

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12398321
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Schmidt; Peter Josef et al.

Swir pcLED and spinel type phosphors emitting in the 1000-1700 nm range

Abstract

A wavelength converting structure is disclosed, the wavelength converting structure including a spinel type SWIR phosphor material having emission wavelengths in the range of 1000 to 1700 nm, the SWIR phosphor material including $AE_{1-x-z}A_zD_{2+0.5(x-y)-z}E_{0.4}Ni_yCr_u$ where $AE=Mg, Zn, Co, \text{ or } Be$, or mixtures thereof, $A=Li, Na, Cu, \text{ or } Ag$, or mixtures thereof, $D=Ga, Al, B, In, \text{ or } Sc$, or mixtures thereof, and $E=Si, Ge, Sn, Ti, Zr, \text{ or } Hf$, or mixtures thereof; where $0 \leq x \leq 1, 0 < y \leq 0.1, 0 \leq z \leq 1, 0 \leq u \leq 0.2$.

Inventors: Schmidt; Peter Josef (Aachen, DE), Wiechert; Detlef (Aachen, DE), Dan; Cristian (Schiphol, NL)

Applicant: LUMILEDS LLC (San Jose, CA)

Family ID: 1000008779126

Assignee: Lumileds LLC (San Jose, CA)

Appl. No.: 17/035233

Filed: September 28, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20210095201 A1	Apr. 01, 2021

Foreign Application Priority Data

EP	19200773	Oct. 01, 2019
----	----------	---------------

Publication Classification

Int. Cl.: C09K11/77 (20060101); C01G15/00 (20060101); C09K11/08 (20060101); C09K11/64 (20060101); H10H20/824 (20250101); H10H20/825 (20250101); H10H20/851 (20250101)

U.S. Cl.:

CPC C09K11/7708 (20130101); C01G15/006 (20130101); C09K11/0883 (20130101); C09K11/641 (20130101); C09K11/7701 (20130101); C09K11/7703 (20130101); C09K11/7734 (20130101); H10H20/824 (20250101); H10H20/8242 (20250101); H10H20/8252 (20250101); H10H20/8513 (20250101); C01P2002/54 (20130101)

Field of Classification Search

CPC: C09K (11/7708); C09K (11/0883); C09K (11/641); C09K (11/7701); C09K (11/7703); C09K (11/7734); H10H (20/8513); H10H (20/8242); H10H (20/8251); H10H (20/824)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2003/0013593	12/2002	Beall et al.	N/A	N/A
2003/0063892	12/2002	Beall	385/129	C03C 13/046
2019/0256769	12/2018	Jia	N/A	C09K 11/77062

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2019-087711	12/2018	JP	N/A

OTHER PUBLICATIONS

Suzuki Takenobu et al., “Optical properties of transparent Li₂O—Ga₂O₃—SiO₂ glass-ceramics embedding Ni-doped nanocrystals”, Applied Physics Letters, AIP Publishing LLC, US, vol. 86, No. 13, Mar. 21, 2005, 3 pages. cited by applicant

Zhigang Gao et al., “Selective doping of Ni²⁺ in highly transparent glass-ceramics containing nano-spinels ZnGa₂O₄ and Zn_{1+x}Ga_{2-2x}Ge_xO₄ for broadband near-infrared fiber amplifiers”, Scientific Reports, vo. 7, No. 1, May 11, 2017, 8 pages. cited by applicant

Extended European Search Report corresponding to EP 19200773.0, dated Apr. 21, 2020, 8 pages. cited by applicant

Primary Examiner: Ha; Nathan W

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) This application claims benefit of priority to European Patent Application No. 19200773.0 filed Oct. 1, 2019.

BACKGROUND

(2) Semiconductor light emitting diodes and laser diodes (collectively referred to herein as “LEDs”) are among the most efficient light sources currently available. The emission spectrum of

an LED typically exhibits a single narrow peak at a wavelength determined by the structure of the device and by the composition of the semiconductor materials from which it is constructed. By suitable choice of device structure and material system, LEDs may be designed to operate at ultraviolet, visible, or infrared wavelengths.

(3) LEDs may be combined with one or more wavelength converting materials (generally referred to herein as “phosphors”) that absorb light emitted by the LED and in response emit light of a longer wavelength. For such phosphor-converted LEDs (“pcLEDs”), the fraction of the light emitted by the LED that is absorbed by the phosphors depends on the amount of phosphor material in the optical path of the light emitted by the LED, for example on the concentration of phosphor material in a phosphor layer disposed on or around the LED and the thickness of the layer.

(4) Phosphor-converted LEDs may be designed so that all of the light emitted by the LED is absorbed by one or more phosphors, in which case the emission from the pcLED is entirely from the phosphors. In such cases the phosphor may be selected, for example, to emit light in a narrow spectral region that is not efficiently generated directly by an LED. Alternatively, pcLEDs may be designed so that only a portion of the light emitted by the LED is absorbed by the phosphors, in which case the emission from the pcLED is a mixture of light emitted by the LED and light emitted by the phosphors. By suitable choice of LED, phosphors, and phosphor composition, such a pcLED may be designed to emit, for example, white light having a desired color temperature and desired color-rendering properties

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 illustrates an embodiment of a wavelength converting structure as part of an illumination device.

(2) FIG. 2 illustrates another embodiment of a wavelength converting structure as part of an illumination device.

(3) FIG. 3 is a cross sectional view of an LED.

(4) FIG. 4 is a cross sectional view of a device with a wavelength converting structure in direct contact with an LED.

(5) FIG. 5 is a cross sectional view of a device with a wavelength converting structure in close proximity to an LED.

(6) FIG. 6 is a cross sectional view of a device with a wavelength converting structure spaced apart from an LED.

(7) FIG. 7 shows the X ray powder diffraction (XRD) pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$.

(8) FIG. 8 shows the powder reflectance and emission (620 nm excitation) spectra of the obtained $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$.

(9) FIG. 9 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4}\text{Ni}_{0.051}$.

(10) FIG. 10 shows the powder reflectance and emission (620 nm excitation) spectra of the obtained $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4}\text{Ni}_{0.051}$.

(11) FIG. 11 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4}\text{Ni}_{0.05}$.

(12) FIG. 12 shows the powder reflectance and emission (620 nm excitation) spectra of the obtained $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4}\text{Ni}_{0.05}$.

(13) FIG. 13 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$.

(14) FIG. 14 shows the powder reflectance and emission (620 nm excitation) spectra of the

obtained Gd.sub.3Ga.sub.3.82AlO.sub.12:Ni.sub.0.04,Zr.sub.0.04,Cr.sub.0.1.

(15) FIG. 15 shows the X ray powder pattern (Cu k alpha radiation) of the obtained Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05.

(16) FIG. 16 shows the powder reflectance spectrum and emission spectrum (for 620 nm excitation) of the obtained Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05.

(17) FIG. 17 shows the thermal quenching behavior of emission under 620 nm excitation of the obtained Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05.

(18) FIG. 18 shows the X ray powder pattern (Cu k alpha radiation) of the obtained Li.sub.0.49Al.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05.

(19) FIG. 19 shows the powder reflectance spectrum and emission spectrum (for 620 nm excitation) of the obtained Li.sub.0.49Al.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05.

(20) FIG. 20 shows the simulated emission spectrum of a pc LED with a phosphor mix.

(21) FIG. 21 shows the mission spectrum of the phosphor converted LED of Example 8 for the visible (left) and IR (right) spectral range.

(22) FIG. 22 shows the total emission spectrum of the pcLED of Example 9.

(23) FIG. 23 shows the total emission spectrum of the pcLED of Example 10.

DETAILED DESCRIPTION

(24) This specification discloses phosphors that can emit infrared (“IR”) radiation in the short wave infrared radiation range (“SWIR”), more specifically, phosphors that can emit infrared radiation having a peak wavelength range 1000-1700 nm. The specification discloses phosphors that can be excited with wavelengths in the 600-670 nm spectral range, and that emit infrared radiation with wavelengths in the 1000-1700 nm spectral range. For economy of language, infrared radiation may be referred to herein as “infrared light,” “IR light,” or “light.”

(25) The specification also discloses devices that include a wavelength converting structure formed to include such SWIR emitting phosphors. In particular the specification discloses light sources that include a primary light source, such as an LED, and a wavelength converting structure having an SWIR phosphor material that emits wavelengths in the 1000-1700 nm range. The phosphor materials can efficiently convert shorter wavelength light from the primary light source into broad-band emission with longer wavelengths.

(26) The phosphor converting structure of the devices disclosed herein may further include additional phosphors. The additional phosphors may allow use of a primary light source in the device that emits light in wavelength ranges other than in the 600-670 nm excitation range of the disclosed SWIR phosphors. The additional phosphors may also allow for more efficient excitation of the SWIR phosphors.

(27) The 1000-1700 nm spectral range is interesting for IR absorption spectroscopy applications where traditional incandescent light sources are being applied. For example, polymers that differ in their macromolecular composition can easily be identified by their unique IR absorption patterns in this wavelength range.

(28) Other applications for light sources emitting in the 1000-1700 nm IR spectral range can be found in the medical field, i.e. in sensors and in endoscopic hyper- or multispectral imaging of tissue where efficient, high intensity light sources are especially needed (see for example: Hayashi et al., A broadband LED source in visible to shortwave-infrared wavelengths for spectral tumor diagnostics, Appl. Phys. Lett. 110, 233701 (2017)).

(29) The disclosed light sources are efficient and allow further miniaturization and cost reduction of spectrometers systems, sensors, and hyper- or multispectral imaging systems that cover the 1000-1700 nm wavelength range.

(30) SWIR Phosphor Compositions

(31) SWIR phosphors for down-converting light from the primary light source into the SWIR emission disclosed herein are phosphor materials crystallized into the spinel, perovskite, and/or garnet structure types, and which are doped with Ni.sup.2+, or Ni.sup.2+ and Cr.sup.3+. Such

SWIR phosphors include Ni^{2+} , or Ni^{2+} and Cr^{3+} , doped XY_2O_4 spinels, ABO_3 perovskites and $\text{M}_3\text{B}_2\text{T}_3\text{O}_{12}$ garnets.

(32) Compositions of Spinel Type SWIR Phosphors

(33) Spinel have the general formula XY_2O_4 , where X is a divalent cation and Y is a trivalent cation, for example, MgAl_2O_4 , and crystallize in the cubic (isometric) crystal system. Normal spinel structures are cubic close-packed oxides with eight tetrahedral and four octahedral sites per formula unit. The tetrahedral spaces are smaller than the octahedral spaces. Y^{3+} ions occupy half the octahedral holes, while X^{2+} ions occupy one-eighth of the tetrahedral holes. Inverse spinel structures have a different cation distribution in that all of the X^{2+} ions and half of the Y^{3+} ions occupy octahedral sites, while the other half of the Y^{3+} ions occupy tetrahedral sites. Most spinel structures are somewhere between the normal and inverse spinel structure.

(34) Compositions of spinels may have $\text{X}=\text{AE}$ ("AE" is alkaline earth metal) with a charge of +2, and a Y cation with a charge of +3. However, the spinel structure also forms if X is a cation with charge +1 and Y is a cation with charge +4.

(35) Compositions of spinel type SWIR phosphors that emit light in the 1000-1700 nm range may be $\text{AE}_{1-x-z}\text{A}_z\text{D}_{0.5(x-y)}\text{E}_u\text{O}_4:\text{Ni}_y\text{Cr}_u$, with $\text{AE}=\text{Mg, Zn, Co, Be}$ or mixtures from this group of divalent atoms, $\text{A}=\text{Li, Na, Cu, Ag}$ or mixtures from this group of monovalent atoms, $\text{D}=\text{Ga, Al, B, In, Sc}$ or mixtures from this group of trivalent atoms and $\text{E}=\text{Si, Ge, Sn, Ti, Zr, Hf}$ or mixtures from this group of tetravalent atoms; where $0 \leq x \leq 1$, $0 < y \leq 0.1$, $0 \leq z \leq 1$, $0 \leq u \leq 0.2$.

(36) Compositions of spinel type SWIR phosphors may have $\text{X}=1$ and $z=0$ (i.e., no AE and no E atoms) and $\text{A}=\text{Li}$ and $\text{D}=\text{Ga}$ and Al, Sc , or a mixture of Al and Sc , with Ga being the main component of D (i.e., having a higher concentration than Al and/or Sc). Compositions of SWIR phosphors may have A atoms and D atoms such as Li and Ga replaced by AE atoms such as Mg ($\text{A}+\text{D}$ replaced by 2 AE to maintain charge neutrality), which the inventors have found leads to a broadening of the emission band and increased emission intensity at lower energies. Substitution of part of the A atoms, such as Li , with AE atoms like Mg can be done without a significant change of properties ($x \leq 1$). Zn can reduce the optical band gap and the luminescence efficiency. Co has about the same size as Mg , Zn or Li and also shows IR emission. The E atom may be Ge because it is known to form inverse spinel structures with e.g. Li and Ga also present

(37) Examples of spinel type SWIR phosphors are the inverse spinel phosphors

$\text{Li}_{0.475}\text{AlGa}_{1.475}\text{O}_4:\text{Ni}_{0.05}$ and

$\text{Li}_{0.225}\text{Mg}_{0.5}\text{Ga}_{2.225}\text{O}_4:\text{Ni}_{0.05}$ with the D cations Ga and Al occupying both the tetrahedral and octahedral sites of the spinel structure. The emission of these phosphors is located in the 1100-1600 nm wavelength range. The absorption and emission bands of these phosphors can be tuned by varying the average size of D cations. The inventors found that D cations larger than Ga , such as In or Sc , lead to a spectroscopic red shift, while cations smaller than Ga , such as Al or B , lead to a spectroscopic blue shift of absorption and emission bands.

(38) Codoping of these inverse spinel SWIR phosphors with Cr^{3+} allows efficient excitation in the blue and red spectral range. The Cr^{3+} ions absorb most of the excitation energy and transfer it to the Ni^{2+} atoms that show broad band luminescence in the 1100-1600 nm wavelength range. An example for such phosphor composition is

$\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_4:\text{Ni}_{0.013}\text{Cr}_{0.05}$.

(39) In the method for synthesizing the spinel type SWIR phosphor compositions, a flux additive may be used. Flux additives for the inverse spinel phosphors herein may be borate compounds such as lithium tetraborate, $\text{Li}_2\text{B}_4\text{O}_7$. When such a flux additive is used, small amounts of boron may be present in the SWIR phosphors after full processing, and such boron may improve the luminescence intensities.

(40) Compositions of Perovskite Type SWIR Phosphors

(41) Perovskites have the general formula ABO_3 , where the A cations are larger than the B cations, and have the same type of crystal structure as $CaTiO_3$. In the ideal (non-distorted) perovskite structure, the B cations are surrounded by 6 X anions in the form of an octahedra. The octahedra are connected with each other via corner sharing to form an ReO_3 -like atomic arrangement with the A cation occupying the 12-fold coordination site formed in the middle of the cube of eight such octahedra.

(42) Compositions of perovskite type SWIR phosphors that emit light in the 1000-1700 nm range are $RE_{1-2p}O_3Ni_pZ_p$ with $RE=La, Gd, Y, Lu, Yb, Nd, Tm, Er$ or mixtures from this group of elements and $T=Al, Ga, Sc, In$, or mixtures from this group of elements, $Z=Ti, Hf, Zr, Si, Ge, Sn$, or mixtures from this group of elements; $0 < p \leq 0.1$.

(43) An example of a perovskite type SWIR phosphor is

$YAl_{0.5}Ga_{0.49}O_3Ni_{0.005}Ge_{0.005}$ showing peak emission in the 1100-1200 nm wavelength range. As for the case of spinel type phosphors, the Ni^{2+} emission band can be shifted by altering the crystal field strength at the activator site, a larger crystal field strength due to a smaller distances $Ni-O$ within the NiO_8 octahedra as a consequence of smaller RE and/or T atoms leads to a spectroscopic blue shift of absorption and emission bands.

(44) Compositions of perovskite type SWIR phosphors may have $RE=Y$ and $T=Ga$. For such compositions, substitution of Y by La or Gd (Lu, Yb) leads to an emission shift to lower (higher) energies. Substitution by Yb, Nd, Tm or Er leads to additional emission in the IR spectral range, typically f-f line emission. Substitution of Ga by Sc or In (Al) leads to an emission shift to lower (higher) energies.

(45) In some compositions of perovskite type SWIR phosphors, Z atoms with charge +4 are used for charge compensation because Ni^{2+} is incorporated on T site with charge 3+; two Ga^{3+} atoms are e.g. substituted by a Ni^{2+} and Zr^{4+} pair.

(46) Compositions of Garnet Type SWIR Phosphors:

(47) Garnets have a general formula $M_3B_2T_3O_{12}$ and may have a cubic structure. In the cubic garnet structure $M_3B_2T_3O_{12}$, the M is typically a rare earth or alkaline earth metal. The large M cations are surrounded by 8 X anions that form a distorted cube or dodecahedron. The smaller B cations are surrounded by 6 X atoms that form an octahedra, and the smallest T atoms are surrounded by 4 X atoms that form a tetrahedra. The REX_8 , BX_6 , and TX_4 units are connected via corner and edge sharing to form a complex 3-dimensional network.

(48) Compositions of garnet type SWIR phosphors that emit light in the 1000-1700 nm range are $RE_3AA_2-2q-sTT_3O_{12}Ni_qZ_qCr_s$ with $RE=La, Gd, Y, Lu, Yb, Nd, Tm, Er$, or mixtures from this group of elements, $AA=Ga, Sc, In, Al$, or Lu , $TT=Al, Ga$, or mixtures from this group of elements, $Z=Ti, Hf, Zr, Si, Ge, Sn$, or mixtures from this group of elements; $0 < q \leq 0.1$, $0 < s \leq 0.2$.

(49) In some garnet type SWIR phosphor compositions, $RE=Gd, Y$ or Lu and $AA=Ga$ and $TT=Ga, Al$. The impact of the various substitutions on the IR emission is the same as described for the perovskites.

(50) An example of a garnet type SWIR phosphor is

$Gd_3Ga_3.82AlO_{12}Cr_{0.1}Ni_{0.04}Zr_{0.04}$, which shows emission in the 1400-1500 nm wavelength range. Cr^{3+} enhances the absorption in the red spectral range and acts as a sensitizer for the Ni^{2+} luminescence.

(51) For the garnet type SWIR phosphors Z atoms with charge +4 may be used for charge compensation because Ni^{2+} is incorporated on A site with charge 3+; two Ga^{3+} atoms are e.g. substituted by a and Zr^{4+} pair.

(52) Illumination Devices Including the SWIR Phosphors

(53) FIG. 1 illustrates a wavelength converting structure **108** that includes at least one of the disclosed luminescent SWIR phosphors. Wavelength converting structure **108** is used in an

illumination device **101**, which includes primary light source **100**. The primary light source **100** may be an LED or any other suitable source including, as examples, resonant cavity light emitting diodes (RCLEDs) and vertical cavity laser diodes (VCSELs). Light source **100** emits a first light **104**. A portion of the first light **104** is incident upon a wavelength converting structure **108**. The wavelength converting structure **108** absorbs the first light **104** and emits second light **112**. The wavelength converting structure **108** may be structured such that little or no first light is part of the final emission spectrum from the device, though this is not required.

(54) Wavelength converting structure **108** may include, for example, one or more of the Ni^{2+} , or Ni^{2+} and Cr^{2+} doped spinel, perovskite, and garnet type SWIR phosphors disclosed herein, such that device **101** emits second light **112** in the 1000-1700 nm wavelength range.

(55) The wavelength converting structure **108** may include an SWIR phosphor that can be excited in the red spectral range. In such case, device **101** may include as a primary light source **100** a red emitting LED, emitting first light **104** in the 600-1000 nm wavelength range. In some embodiments, light source **100** is an AlInGaP type emitter and may emit first light **104** having wavelengths in the 600-650 nm range. In other embodiments, light source **100** may be an InGaAs type emitter and may emit first light in the 700-1000 nm wavelength range, to excite the disclosed Ni^{2+} doped SWIR phosphors directly via the energetically lowest lying absorption transition.

(56) In an example, device **101** may have a wavelength converting structure **108** that includes $\text{Li}_{0.5-0.5x}(\text{Ga}, \text{Sc})_{2.5-0.5x-y}\text{O}_4\text{Ni}_x\text{Cr}_y$ (where $0 \leq x \leq 1$, $0 < y \leq 0.1$, $0 \leq z \leq 1$, $0 \leq u \leq 0.2$) spinel type SWIR phosphor, and may use as primary light source **100** a 620-630 nm emitting AlInGaP type LED. More specifically, device **101** may have a wavelength converting structure **108** that includes $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_4\text{Ni}_{0.013}\text{Cr}_{0.05}$ spinel type SWIR phosphor, and may use as primary light source **100** a 622 nm emitting AlInGaP type LED.

(57) The wavelength converting structure **108** described with respect to FIG. 1 can be manufactured, for example, in powder form, in ceramic form, or in any other suitable form. The wavelength converting structure **108** may be formed into one or more structures that are formed separately from and can be handled separately from the light source, such as a prefabricated glass or ceramic tile, or may be formed into a structure that is formed in situ with the light source, such as a conformal or other coating formed on or above the source.

(58) In some embodiments, the wavelength converting structure **108** may be powders that are dispersed for example in a transparent matrix, a glass matrix, a ceramic matrix, or any other suitable material or structure. SWIR phosphor dispersed in a matrix may be, for example, singulated or formed into a tile that is disposed over a light source. The glass matrix may be for example a low melting glass with a softening point below 1000°C ., or any other suitable glass or other transparent material. The ceramic matrix material can be for example a fluoride salt such as CaF_2 or any other suitable material.

(59) The wavelength converting structure **108** may be used in powder form, for example by mixing the powder SWIR phosphor with a transparent material such as silicone and dispensing or otherwise disposing it in a path of light. In powder form, the average particle size (for example, particle diameter) of the SWIR phosphors may be at least $1 \mu\text{m}$ in some embodiments, no more than $50 \mu\text{m}$ in some embodiments, at least $5 \mu\text{m}$ in some embodiments, and no more than $20 \mu\text{m}$ in some embodiments. Individual SWIR phosphor particles, or powder SWIR phosphor layers, may be coated with one or more materials such as a silicate, a phosphate, and/or one or more oxides in some embodiments, for example to improve absorption and luminescence properties and/or to increase the material's functional lifetime.

(60) FIG. 2 illustrates another embodiment in which a wavelength converting structure including one or more of the disclosed SWIR phosphor materials may further be combined with a second phosphor system. In FIG. 2, the wavelength converting structure **218** includes an SWIR phosphor portion **208** and a second phosphor portion **202** as part of an illumination device **201**. In FIG. 2, a

light source **200** may be an LED or any other suitable source, (including as examples resonant cavity light emitting diodes (RCLEDs) and vertical cavity laser diodes (VCSELs). Light source **200** emits first light **204**. First light **204** is incident upon wavelength converting structure **218**, which includes an SWIR phosphor portion **208** including one or more of the SWIR phosphors disclosed herein, and a second phosphor system **202**. A portion of the first light **204** is incident on a second phosphor portion **202** of the wavelength converting structure **218**. The second phosphor **202** absorbs the first light **204** and emits third light **206**. The third light **206** may have a wavelength range that is within the excitation range of the SWIR phosphor in the SWIR phosphor portion **208** of the wavelength converting structure **218**. The third light **206** is incident on the SWIR phosphor portion **208**. The SWIR phosphor portion **208** absorbs all or a portion of the third light **206** and emits fourth light **210**. Additionally, a portion of the first light **204** may be incident on an SWIR phosphor portion **208** of the wavelength converting structure **218**. The SWIR phosphor portion **208** may absorb the first light **204** and emit second light **212**, or first light **204** may pass through the SWIR phosphor portion **208**.

(61) The wavelength converting structure **218** including an SWIR phosphor **208** and second phosphor **202** may be structured such that little or no first light or third light is part of the final emission spectrum from the device, though this is not required.

(62) The SWIR phosphor portion **208** of wavelength converting structure **218** may include, for example, one or more of the Ni²⁺, or Ni²⁺ and Cr²⁺ spinel, perovskite, and garnet SWIR phosphors disclosed herein, such that device **202** emits light in the 1000-1700 nm wavelength range.

(63) Any suitable second phosphor may be used in the second phosphor system **202**. The second phosphor system **202** can be used with SWIR phosphor portion **208** to widen the spectral range that allows efficient excitation of the SWIR phosphor, and thus increase number of the types of primary light sources **200** that may be used in device **201**. That is, the second phosphor system **202** may include a second phosphor that absorbs first light **204** from a primary light source **200** that emits light outside of the wavelength range required to excite the SWIR phosphor. For instance, the second phosphor system **202** may absorb first light **204** emitted from a blue or green LED as primary light source **200**. The second phosphor system **202** then emits third light **206** in the red spectral range. The third light **206** emitted from second phosphor system **202** excites the SWIR phosphor in SWIR phosphor portion **208**.

(64) For example, device **201** may include green to red emitting phosphors, such as Eu²⁺ phosphors, added as the second phosphor system **202**, and may use a blue emitting LED as the primary light source **200**. Examples of a red emitting phosphor for use in second phosphor system **202** include (Sr,Ca)AlSiN₃:Eu and (Ba,Sr,Ca)₂Si₅-xAl_xO_xN_{8-x}:Eu.

(65) In an example device, primary light source **200** may be a blue light emitting InGaN type emitter. The wavelength converting structure **218** may include an orange-red emitting (Ba,Sr)₂Si₅N₈:Eu phosphor as the second phosphor system **202** and a Li_{0.5-0.5x}(Ga,Sc)_{2.5-0.5x-y}O₄Ni_xCr_y spinel phosphor as the SWIR phosphor portion **212**. In particular, device **201** may include as a primary light source **200** a 440-455 nm emitting InGaN type emitter, and a wavelength converting structure **218** that includes orange-red emitting phosphor (Ba_{0.4}Sr_{0.6})₂-xSi₅N₈:Eu_{0.02} and a Li_{0.49}Sc_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05} SWIR phosphor.

(66) The second phosphor system **202** may include Cr³⁺ doped phosphors that emit in the 700-1000 nm wavelength range and that can be excited in the blue to green and red spectral ranges. The emission light of such Cr³⁺ phosphors being reabsorbed by Ni²⁺ doped SWIR phosphor disclosed herein.

(67) The second phosphor system **202** may include other Ni²⁺ phosphor systems that are known from the literature. Examples include LaMgGa₁₁O₁₉:Ni, MgO:Ni, MgF₂:Ni, Ga₂O₃:Ni,Ge, or garnets of composition RE₂AEM₂TV₃O₁₂:Ni

(RE=Y, La, Lu, Gd, Nd, Yb, Tm, Er; AE=Ca, Sr; TV=Si, Ge).

(68) The wavelength converting structure **218** including SWIR phosphor **208** and the second phosphor **202** described with respect to FIG. **2** can be manufactured, for example, in powder form, in ceramic form, or in any other suitable form. The SWIR phosphor **208** and the second phosphor **202** may be formed into one or more structures that are formed separately from and can be handled separately from the light source, such as a prefabricated glass or ceramic tile, or may be formed into a structure that is formed in situ with the light source, such as a conformal or other coating formed on or above the source.

(69) The SWIR phosphor **208** and the second phosphor **202** may be mixed together in a single wavelength converting layer, or formed as separate wavelength converting layers. In a wavelength converting structure with separate wavelength converting layers, SWIR phosphor **208** and the second phosphor **202** may be stacked such that the second phosphor **202** may be disposed between the SWIR phosphor **208** and the light source, or the SWIR phosphor **208** may be disposed between the second phosphor **202** and the light source.

(70) In some embodiments, the SWIR phosphor **208** and the second phosphor **202** may be powders that are dispersed for example in a transparent matrix, a glass matrix, a ceramic matrix, or any other suitable material or structure. Phosphor dispersed in a matrix may be, for example, singulated or formed into a tile that is disposed over a light source. The glass matrix may be for example a low melting glass with a softening point below 1000° C., or any other suitable glass or other transparent material. The ceramic matrix material can be for example a fluoride salt such as CaF₂ or any other suitable material.

(71) The SWIR phosphor **208** and second phosphor **202** may be used in powder form, for example by mixing the powder phosphor with a transparent material such as silicone and dispensing or otherwise disposing it in a path of light. In powder form, the average particle size (for example, particle diameter) of the phosphors may be at least 1 μm in some embodiments, no more than 50 μm in some embodiments, at least 5 μm in some embodiments, and no more than 20 μm in some embodiments. Individual phosphor particles, or powder phosphor layers, may be coated with one or more materials such as a silicate, a phosphate, and/or one or more oxides in some embodiments, for example to improve absorption and luminescence properties and/or to increase the material's functional lifetime.

(72) As shown in FIGS. **1** and **2**, an illumination device may include a wavelength converting structure that may be used, for example, with light source **100**, **200**. Light source **100**, **200** may be a light emitting diode (LED). Light emitted by the light emitting diode is absorbed by the phosphors in the wavelength converting structure according to embodiments and emitted at a different wavelength. FIG. **3** illustrates one example of a suitable light emitting diode, a III-nitride LED that emits blue light for use in an illumination device such as those disclosed with respect to FIG. **2**, in which the SWIR phosphor is combined with a second phosphor that absorbs the blue light and emits the SWIR light.

(73) Though in the example below the semiconductor light emitting device is a III-nitride LED that emits blue or UV light, semiconductor light emitting devices besides LEDs such as laser diodes and semiconductor light emitting devices made from other materials systems such as other III-V materials, III-phosphide, III-arsenide, II-VI materials, ZnO, or Si-based materials may be used, as determined by, for example, the range of wavelengths needed to excite the SWIR phosphor, or combination of SWIR phosphor and second phosphor, in the wavelength converting structure.

(74) FIG. **3** illustrates a III-nitride LED **1** that may be used in embodiments of the present disclosure. Any suitable semiconductor light emitting device may be used and embodiments of the disclosure are not limited to the device illustrated in FIG. **3**. The device of FIG. **3** is formed by growing a III-nitride semiconductor structure on a growth substrate **10** as is known in the art. The growth substrate is often sapphire but may be any suitable substrate such as, for example, SiC, Si, GaN, or a composite substrate. A surface of the growth substrate on which the III-nitride

semiconductor structure is grown may be patterned, roughened, or textured before growth, which may improve light extraction from the device. A surface of the growth substrate opposite the growth surface (i.e. the surface through which a majority of light is extracted in a flip chip configuration) may be patterned, roughened or textured before or after growth, which may improve light extraction from the device.

(75) The semiconductor structure includes a light emitting or active region sandwiched between n- and p-type regions. An n-type region **16** may be grown first and may include multiple layers of different compositions and dopant concentration including, for example, preparation layers such as buffer layers or nucleation layers, and/or layers designed to facilitate removal of the growth substrate, which may be n-type or not intentionally doped, and n- or even p-type device layers designed for particular optical, material, or electrical properties desirable for the light emitting region to efficiently emit light. A light emitting or active region **18** is grown over the n-type region. Examples of suitable light emitting regions include a single thick or thin light emitting layer, or a multiple quantum well light emitting region including multiple thin or thick light emitting layers separated by barrier layers. A p-type region **20** may then be grown over the light emitting region. Like the n-type region, the p-type region may include multiple layers of different composition, thickness, and dopant concentration, including layers that are not intentionally doped, or n-type layers.

(76) After growth, a p-contact is formed on the surface of the p-type region. The p-contact **21** often includes multiple conductive layers such as a reflective metal and a guard metal which may prevent or reduce electromigration of the reflective metal. The reflective metal is often silver but any suitable material or materials may be used. After forming the p-contact **21**, a portion of the p-contact **21**, the p-type region **20**, and the active region **18** is removed to expose a portion of the n-type region **16** on which an n-contact **22** is formed. The n- and p-contacts **22** and **21** are electrically isolated from each other by a gap **25** which may be filled with a dielectric such as an oxide of silicon or any other suitable material. Multiple n-contact vias may be formed; the n- and p-contacts **22** and **21** are not limited to the arrangement illustrated in FIG. 3. The n- and p-contacts may be redistributed to form bond pads with a dielectric/metal stack, as is known in the art.

(77) In order to form electrical connections to the LED **1**, one or more interconnects **26** and **28** are formed on or electrically connected to the n- and p-contacts **22** and **21**. Interconnect **26** is electrically connected to n-contact **22** in FIG. 3. Interconnect **28** is electrically connected to p-contact **21**. Interconnects **26** and **28** are electrically isolated from the n- and p-contacts **22** and **21** and from each other by dielectric layer **24** and gap **27**. Interconnects **26** and **28** may be, for example, solder, stud bumps, gold layers, or any other suitable structure.

(78) The substrate **10** may be thinned or entirely removed. In some embodiments, the surface of substrate **10** exposed by thinning is patterned, textured, or roughened to improve light extraction.

(79) Any suitable light emitting device may be used in light sources according to embodiments of the disclosure. The invention is not limited to the particular LED illustrated in FIG. 3. The light source, such as, for example, the LED illustrated in FIG. 3, is illustrated in the following FIGS. 4, 5 and 6 by block **1**.

(80) FIGS. 4, 5, and 6 illustrate devices that combine an LED **1** and a wavelength converting structure **30**. The wavelength converting structure **30** may be, for example, wavelength converting structure **108** including an SWIR phosphor as shown in FIG. 1, or wavelength converting structure **218** having an SWIR phosphor and a second phosphor as shown in FIG. 2, according to the embodiments and examples described above.

(81) In FIG. 4, the wavelength converting structure **30** is directly connected to the LED **1**. For example, the wavelength converting structure may be directly connected to the substrate **10** illustrated in FIG. 3, or to the semiconductor structure, if the substrate **10** is removed.

(82) In FIG. 5, the wavelength converting structure **30** is disposed in close proximity to LED **1**, but not directly connected to the LED **1**. For example, the wavelength converting structure **30** may be

separated from LED 1 by an adhesive layer 32, a small air gap, or any other suitable structure. The spacing between LED 1 and the wavelength converting structure 30 may be, for example, less than 500 μm in some embodiments.

(83) In FIG. 6, the wavelength converting structure 30 is spaced apart from LED 1. The spacing between LED 1 and the wavelength converting structure 30 may be, for example, on the order of millimeters in some embodiments. Such a device may be referred to as a “remote phosphor” device.

(84) The wavelength converting structure 30 may be square, rectangular, polygonal, hexagonal, circular, or any other suitable shape. The wavelength converting structure may be the same size as LED 1, larger than LED 1, or smaller than LED 1.

(85) Multiple wavelength converting materials and multiple wavelength converting structures can be used in a single device. Examples of wavelength converting structures include luminescent ceramic tiles; powder phosphors that are disposed in transparent material such as silicone or glass that is rolled, cast, or otherwise formed into a sheet, then singulated into individual wavelength converting structures; wavelength converting materials such as powder phosphors that are disposed in a transparent material such as silicone that is formed into a flexible sheet, which may be laminated or otherwise disposed over an LED 1, wavelength converting materials such as powder phosphors that are mixed with a transparent material such as silicone and dispensed, screen printed, stenciled, molded, or otherwise disposed over LED 1; and wavelength converting materials that are coated on LED 1 or another structure by electrophoretic, vapor, or any other suitable type of deposition.

(86) A device may also include other wavelength converting materials in addition to the SWIR phosphor and a second phosphor described above, such as, for example, conventional phosphors, organic phosphors, quantum dots, organic semiconductors, II-VI or III-V semiconductors, II-VI or III-V semiconductor quantum dots or nanocrystals, dyes, polymers, or other materials that luminesce.

(87) Multiple wavelength converting materials may be mixed together or formed as separate structures.

(88) In some embodiments, other materials may be added to the wavelength converting structure or the device, such as, for example, materials that improve optical performance, materials that encourage scattering, and/or materials that improve thermal performance.

Examples

(89) 1) Synthesis of $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$. Compositions of $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$ were synthesized from powders of lithium carbonate (Alfa Aesar, 99.998%), gallium oxide (Molycorp, UHP grade), scandium oxide (MIRE Ltd., 5N) and nickel oxide (Alfa Aesar, 99.99%). 1.595 g of the lithium carbonate, 17.914 g of the gallium oxide, 0.567 g of the scandium oxide, and 0.301 g of the nickel oxide were mixed by ball milling and fired twice at 1300° C. with intermediate milling followed by ball milling, powder washing in water, and final screening.

(90) The obtained powder of $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$ crystallized in the inverse spinel structure with a cubic lattice constant of 8.223 Å and a density of 5.812 g/cm³.

(91) FIG. 7 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$. FIG. 8 shows the powder reflectance 801 and emission (620 nm excitation) spectra 802 of the obtained $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4}\text{Ni}_{0.051}$.

(92) 2) Synthesis of $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4}\text{Ni}_{0.051}$. Compositions of $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4}\text{Ni}_{0.051}$ were synthesized from powders of lithium carbonate (Alfa Aesar, 99.998%), gallium oxide (Molycorp, UHP grade), aluminum oxide (Baikowski, 4N) and nickel oxide (Alfa Aesar, 99.99%). 1.968 g of the lithium carbonate, 13.42 g

of the gallium oxide, 5.123 g of the aluminum oxide, and 0.375 g of the nickel oxide were mixed by ball milling and fired twice at 1325° C. with intermediate milling followed by ball milling, powder washing in water, and final screening.

(93) The obtained $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4.051}\text{Ni}_{0.051}$ powder crystallized in the inverse spinel structure with a cubic lattice constant of 8.086 Å and a density of 5.001 g/cm³.

(94) FIG. 9 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4.051}\text{Ni}_{0.051}$. FIG. 10 shows the powder reflectance **1001** and emission (620 nm excitation) spectra **1002** of the obtained $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4.051}\text{Ni}_{0.051}$.

(95) Synthesis of $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.05}\text{Ni}_{0.05}$. Compositions of $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.05}\text{Ni}_{0.05}$ were synthesized from powders of lithium carbonate (Merck, p.a.), magnesium oxide (Merck, p.a.), gallium oxide (Molycorp, UHP grade), scandium oxide (MIRE Ltd., 5N), and nickel oxide (Alfa Aesar, 99.99%). 0.935 g of the lithium carbonate, 1.854 g of the magnesium oxide, 18.755 g of the gallium oxide, 0.317 g of the scandium oxide, and 0.344 g of the nickel oxide were mixed by ball milling and fired twice at 1100° C. and 1350° C., respectively, with intermediate milling followed by ball milling, powder washing in water, and final screening.

(96) The obtained $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.05}\text{Ni}_{0.05}$ powder crystallized in the inverse spinel structure with a cubic lattice constant of 8.2312 Å and a density of 5.178 g/cm³.

(97) FIG. 11 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.05}\text{Ni}_{0.05}$. FIG. 12 shows the powder reflectance **1201** and emission (620 nm excitation) spectra **1202** of the obtained $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.05}\text{Ni}_{0.05}$.

(98) 4) Synthesis of $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$. Compositions of $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$ were synthesized from powders of gallium oxide (Alfa Aesar, Puratronic), gadolinium fluoride (Rhodia, 4N), zirconium oxide (Daichi, 5N), nickel oxide (Alfa Aesar, 4N), gadolinium oxide (Liyang Solvay, 5N), chromium oxide (Alfa Aesar, 2N5), and aluminum oxide (Baikowski, 4N). 7.4711 g of the gallium oxide, 0.1326 g of the gadolinium fluoride, 0.1026 g of the zirconium oxide, 0.0616 g of the nickel oxide, 11.2757 g of the gadolinium oxide, 0.1568 g of the chromium oxide, and 1.0864 g of the aluminum oxide were wet mixed by ball milling in ethanol followed by drying. The powder mixture was fired 1500° C. for at least 8 hrs and cooled to room temperature. The obtained $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$ powder cake was de-aggregated by ball milling, washed with water, and finally screened to obtain the desired particle size distribution.

(99) The obtained $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$ powder crystallized in the garnet structure with a cubic lattice constant of 12.312 Å and a density of 6.906 g/cm³.

(100) FIG. 13 shows the X ray powder pattern (Cu k alpha radiation) of the obtained $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$. FIG. 14 shows the powder reflectance **1401** and emission (620 nm excitation) spectra **1402** of the obtained $\text{Gd}_{0.3}\text{Ga}_{3.82}\text{AlO}_{12}\text{Ni}_{0.04}\text{Zr}_{0.04}\text{Cr}_{0.1}$.

(101) 5) Synthesis of $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_{4.013}\text{Cr}_{0.05}$. Compositions of $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_{4.013}\text{Cr}_{0.05}$ were synthesized from powders of lithium carbonate (Merck p.a.), gallium oxide (Molycorp UHP), nickel oxide (Sigma Aldrich, 99%), scandium oxide (MIRE Ltd., 5N), lithium tetraborate (Alfa Aesar, 98%), and chromium oxide (Alfa Aesar, >98%). 1.517 g of the lithium carbonate, 18.654 g of the gallium oxide, 0.078 g of the nickel oxide, 0.287 g of the scandium oxide, 0.176 g of the

lithium tetraborate, and 0.316 g of the chromium oxide were mixed by ball milling and fired at 1300° C. for 4 hrs under ambient conditions. The raw product was milled, washed with diluted hydrochloric acid and water. After screening a powder sample was obtained that crystallized in the cubic spinel structure type with a lattice constant of 8.2127 Å and a density of 5.769 g/cm³. (102) FIG. 15 shows the X ray powder pattern (Cu k alpha radiation) of the obtained Li_{0.49}Sc_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05}. FIG. 16 shows the powder reflectance spectrum 1601 and emission spectrum (for 620 nm excitation) 1602, and FIG. 17 shows the thermal quenching behavior of emission under 620 nm excitation of the obtained Li_{0.49}Sc_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05}.

(103) 6) Synthesis of Li_{0.49}Al_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05}. Compositions of Li_{0.49}Al_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05} were synthesized from powders of lithium carbonate (Merck p.a.), gallium oxide (Molycorp UHP), nickel oxide (Sigma Aldrich, 99%), aluminum oxide (Baikowski, >99%), lithium tetraborate (Alfa Aesar, 98%), and chromium oxide (Alfa Aesar, >98%). 1.522 g of the lithium carbonate, 18.724 g of the gallium oxide, 0.078 g of the nickel oxide, 0.213 g of the aluminum oxide, 0.176 g of the lithium tetraborate, and 0.317 g of the chromium oxide were mixed by ball milling and fired at 1320° C. for 4 hrs under ambient conditions. The raw product was milled, washed with diluted hydrochloric acid and water. After screening a powder sample was obtained that crystallized in the cubic spinel structure type with a lattice constant of 8.1975 Å and a density of 5.779 g/cm³.

(104) FIG. 18 shows the X ray powder pattern (Cu k alpha radiation) of the obtained Li_{0.49}Al_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05}. FIG. 19 shows the powder reflectance spectrum 1901 and emission spectrum 1902 (for 620 nm excitation) of the obtained Li_{0.49}Al_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05}.

(105) 7) Example of a Phosphor Converted LED with a 2-Phosphor Mix. FIG. 20 shows a simulated emission spectrum of a phosphor converted LED device that will consist of a 625 nm peak emitting AlInGaP LED combined with a mixture of

Li_{0.536}Al_{1.01}Ga_{1.44}O₄Ni_{0.051} spinel type phosphor synthesized as described with respect to Example 2 and

Gd_{0.3}Ga_{3.82}AlO₁₂Ni_{0.04}Zr_{0.04}Cr_{0.1} garnet type phosphor synthesized as described with respect to Example 4. By combining these phosphors an IR spectrum with a broad FWHM>350 nm covering the wavelength range of 1100-1700 nm can be realized.

(106) 8) Example of a Phosphor Converted LED with Red Emitting Pump LED. The Li_{0.49}Sc_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05} spinel type phosphor synthesized as described in Example 5 was mixed with a PDMS type silicone having a refractive index n_d=1.41 and a viscosity of 4 Pa s and with a loading of 220 wt % (i.e. 220 g phosphor in 100 g silicone, 69 wt % phosphor in the silicon) with respect to the silicone weight. The suspension was then dispensed into a 2.7×2.0 mm² lead frame LED package equipped with a 622 nm emitting LED die that emits a radiation power of 195 mW at 350 mA and room temperature.

(107) FIG. 21 shows the emission spectrum of the phosphor converted LED of this Example 8 for the visible 2101 and IR 2102 spectral range. The phosphor converted LED shows the same emission band as shown in FIG. 16, except for a small dip in the emission profile at around 1190 nm due to absorption of the silicone encapsulant used. The total emitted IR radiation power in the 1000-1600 nm spectral range is 50-60 mW (power conversion red/IR=25-30% (FIG. 21).

(108) 9) Example of a Phosphor Converted LED with Blue Emitting InGaN Pump LED. The Li_{0.49}Sc_{0.05}Ga_{2.384}O₄Ni_{0.013}Cr_{0.05} spinel type phosphor synthesized as described in Example 5 was mixed with a polydimethyl siloxane type silicone encapsulant (weight ratio phosphor/silicone=0.45) and dispensed into 2720 type leadframe LED packages of a size of 2.7 mm×2.0 mm×0.6 mm (L×W×H) equipped with 450 nm emitting InGaN dies (550 mW output power at 350 mA at 25° C. if filled with the same silicone as used for Example 8 above).

(109) FIG. 22 shows the total emission spectrum of the pcLED of this Example 9 for 350 mA drive current. In the spectral range of 1000-1700 nm, the LED shows an infrared output power of 171 mW.

(110) 10) Phosphor Converted LED with Blue Emitting InGaN Pump LED and Additional Orange-Red Emitting (Ba.sub.0.4Sr.sub.0.6).sub.1.98Si.sub.5N.sub.8:Eu.sub.0.02 phosphor. The Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013,Cr.sub.0.05 phosphor synthesized as described in Example 5 was mixed with (Ba.sub.0.4Sr.sub.0.6).sub.1.98Si.sub.5N8:Eu.sub.0.02 phosphor and with a polydimethyl siloxane type silicone encapsulant (weight ratio phosphor/silicone=0.45, weight ratio IR phosphor/orange-red phosphor=3) and dispensed into 2720 type leadframe LED packages of a size of 2.7 mm×2.0 mm×0.6 mm (L×W×H) equipped with 450 nm emitting InGaN dies (550 mW output power at 350 mA at 25° C. if filled with the same silicone as used for example 8 above).

(111) (Ba.sub.0.4Sr.sub.0.6).sub.1.98Si.sub.5N8:Eu.sub.0.02 phosphor was made by mixing BaH₂ (Materion, >99%), SrH₂ (Materion, >99%), Eu₂O₃ (Neo, >99.9%) and Si₃N₄ (UBE, >98%) under inert conditions and firing the mixture twice with milling in-between the firings under forming gas at 1680° C. The phosphor is then washed in diluted mineral acid, water and ethanol followed by ball milling.

(112) FIG. 23 shows the total emission spectrum of Example 10 for 350 mA drive current. In the spectral range 1000-1700 nm the LED shows an infrared output power of 139 mW.

(113) This disclosure is illustrative and not limiting. Further modifications will be apparent to one skilled in the art in light of this disclosure and are intended to fall within the scope of the appended claims

Claims

1. A wavelength converting structure comprising an SWIR phosphor material having emission wavelength in the range of 1000 to 1700 nm, the SWIR phosphor material represented by formula: AE.sub.1-x-zA.sub.z+0.5(x-y)D.sub.2+0.5(x-y)-z-uE.sub.zO.sub.4:Ni.sub.y, Cr.sub.u where AE=Mg, Zn, Co, or Be, or mixtures thereof, A=Li, Na, Cu, or Ag, or mixtures thereof, D=Ga, Al, B, In, or Sc, or mixtures thereof, and E=Si, Ge, Sn, Ti, Zr, or Hf, or mixtures thereof; where 0≤x≤1, 0<y≤0.1, 0≤z≤1, 0≤u≤0.2, 0≤1-x-z, and 0≤z+0.5(x-y).
2. The wavelength converting structure of claim 1, wherein x=1, z=0, A=Li, and D=Ga, Al, Sc, or a mixture of Al and Sc.
3. The wavelength converting structure of claim 1, wherein x=1, z=0, A=Li, and D=Ga, Sc, or a mixture of Ga and Sc.
4. The wavelength converting structure of claim 1, wherein the SWIR phosphor is Li.sub.0.475AlGa.sub.1.475O.sub.4:Ni.sub.0.05, Li.sub.0.225Mg.sub.0.5Ga.sub.2.225O.sub.4:Ni.sub.0.05, Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013, Cr.sub.0.05, Li.sub.0.532Ga.sub.2.35Sc.sub.0.1O.sub.4:Ni.sub.0.051, Li.sub.0.536Al.sub.1.01Ga.sub.1.44O.sub.4:Ni.sub.0.051, Li.sub.0.273Mg.sub.0.5Sc.sub.0.05Ga.sub.2.16O.sub.4:Ni.sub.0.05, or Cr.sub.0.1, Li.sub.0.49Sc.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013, Cr.sub.0.05, Li.sub.0.49Al.sub.0.05Ga.sub.2.384O.sub.4:Ni.sub.0.013, Cr.sub.0.05.
5. A device comprising wavelength converting structure of claim 1 and a light source, the light source configured to emit a first light, the wavelength converting structure disposed in a path of the first light, wherein the SWIR phosphor material absorbs the first light and emits a second light, the second light having a wavelength range of 1000 to 1700 nm.
6. The device of claim 5, wherein the light source comprises an AlInGaP LED and x=1, z=0, A=Li, and D=Ga, Sc, or a mixture of Ga and Sc.

7. The device of claim 5, wherein the wavelength converting structure comprises a second phosphor material, wherein the second phosphor material absorbs the first light emitted by the light source and emits a third light, and the SWIR phosphor material absorbs the third light and emits a fourth light, the fourth light having a wavelength range of 1000 to 1700 nm.
8. The device of claim 7, wherein the second phosphor material is a green to red emitting phosphor and the light source is a blue emitting LED.
9. The device of claim 8, wherein the second phosphor material is represented by formula $(\text{Sr,Ca})\text{AlSiN}_{3.3}\text{Eu}$ or by formula $(\text{Ba,Sr,Ca})_{2.5-x}\text{Si}_{5-x}\text{Al}_x\text{O}_x\text{N}_{8-x}\text{Eu}$.
10. The device of claim 9, wherein $x=1$, $z=0$, $A=\text{Li}$, and $D=\text{Ga}$, Sc , or a mixture of Ga and Sc and the second phosphor material is represented by formula $(\text{Ba,Sr})_{2.5}\text{Si}_5\text{N}_{8.8}\text{Eu}$, and the light source is a blue light emitting InGaN LED.
11. The device of claim 7, wherein the second phosphor is $\text{LaMgGa}_{11}\text{O}_{19}\text{Ni}$, MgO:Ni , $\text{MgF}_{2.2}\text{Ni}$, $\text{Ga}_{20}\text{Si}_3\text{Ni}$, Ge , or a garnet type phosphor represented by formula $\text{RE}_{2.2}\text{AEM.g}_{2.3}\text{TV}_{3.12}\text{Ni}$ ($\text{RE}=\text{Y}$, La , Lu , Gd , Nd , Yb , Tm , Er ; $\text{AE}=\text{Ca}$, Sr ; $\text{TV}=\text{Si}$, Ge).
12. The device of claim 7, wherein the SWIR phosphor material is $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_{4.4}\text{Ni}_{0.013}$, $\text{Cr}_{0.05}$, the second phosphor material is $(\text{Ba}_{0.4}\text{Sr}_{0.6})_{1.98}\text{Si}_{5.5}\text{N}_{8.8}\text{Eu}_{0.02}$ and the light source comprises an InGaN LED.
13. A luminescent material that emits light having a peak wavelength in the range of 1000 nm to 1700 nm, the luminescent material represented by formula: $\text{AE}_{1-x-z}\text{A}_{z+0.5(x-y)}\text{D}_{2+0.5(x-y)-z}\text{E}_u\text{O}_{4.4}\text{Ni}_y$, Cr_u where $\text{AE}=\text{Mg}$, Zn , Co , or Be , or mixtures thereof, $A=\text{Li}$, Na , Cu , or Ag , or mixtures thereof, $D=\text{Ga}$, Al , B , In , or Sc , or mixtures thereof, and $E=\text{Si}$, Ge , Sn , Ti , Zr , or Hf , or mixtures thereof; where $0 \leq x \leq 1$, $0 < y \leq 0.1$, $0 \leq z \leq 1$, $0 \leq u \leq 0.2$, $0 \leq 1-x-z$, and $0 \leq z+0.5(x-y)$.
14. The luminescent material of claim 13, wherein $x=1$, $z=0$, $A=\text{Li}$, and $D=\text{Ga}$, Al , Sc , or a mixture of Al and Sc .
15. The luminescent material of claim 13, wherein $x=1$, $z=0$, $A=\text{Li}$, and $D=\text{Ga}$, Sc , or a mixture of Ga and Sc .
16. The luminescent material of claim 13, the luminescent material is $\text{Li}_{0.475}\text{AlGa}_{1.475}\text{O}_{4.4}\text{Ni}_{0.05}$, $\text{Li}_{0.225}\text{Mg}_{0.5}\text{Ga}_{2.225}\text{O}_{4.4}\text{Ni}_{0.05}$, $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_{4.4}\text{Ni}_{0.013}$, $\text{Cr}_{0.05}$, $\text{Li}_{0.532}\text{Ga}_{2.35}\text{Sc}_{0.1}\text{O}_{4.4}\text{Ni}_{0.051}$, $\text{Li}_{0.536}\text{Al}_{1.01}\text{Ga}_{1.44}\text{O}_{4.4}\text{Ni}_{0.051}$, $\text{Li}_{0.273}\text{Mg}_{0.5}\text{Sc}_{0.05}\text{Ga}_{2.16}\text{O}_{4.4}\text{Ni}_{0.05}$, $\text{Cr}_{0.1}$, $\text{Li}_{0.49}\text{Sc}_{0.05}\text{Ga}_{2.384}\text{O}_{4.4}\text{Ni}_{0.013}$, $\text{Cr}_{0.05}$, or $\text{Li}_{0.49}\text{Al}_{0.05}\text{Ga}_{2.384}\text{O}_{4.4}\text{Ni}_{0.013}$, $\text{Cr}_{0.05}$.
-