

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408404
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Shimizu; Tatsuo

Method for manufacturing semiconductor device, semiconductor device, inverter circuit, driving device, vehicle, and elevator

Abstract

Provided is a method for manufacturing a semiconductor device, the method including: performing first ion implantation ion-implanting a p-type impurity into a silicon carbide layer; performing second ion implantation ion-implanting carbon (C) into the silicon carbide layer; performing a first heat treatment activating the p-type impurity; performing a first oxidation treatment oxidizing the silicon carbide layer; performing an etching treatment etching the silicon carbide layer in an atmosphere containing hydrogen gas; forming a first metal film containing at least one metal element selected from the group consisting of nickel, palladium, platinum, and chromium; performing a second heat treatment causing the silicon carbide layer to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming a second metal film having a chemical composition different from a chemical composition of the first metal film.

Inventors:	Shimizu; Tatsuo (Shinagawa, JP)
Applicant:	KABUSHIKI KAISHA TOSHIBA (Tokyo, JP)
Family ID:	88067375
Assignee:	KABUSHIKI KAISHA TOSHIBA (Tokyo, JP)
Appl. No.:	17/822970
Filed:	August 29, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230299152 A1	Sep. 21, 2023

Foreign Application Priority Data

JP	2022-041805	Mar. 16, 2022
----	-------------	---------------

Publication Classification

Int. Cl.: **H10D64/01** (20250101); **H01L21/04** (20060101); **H10D12/01** (20250101); **H10D62/832** (20250101); **H10D64/62** (20250101); H10D30/66 (20250101); H10D62/834 (20250101)

U.S. Cl.:

CPC **H10D64/01** (20250101); **H01L21/0485** (20130101); **H10D12/031** (20250101); **H10D62/8325** (20250101); **H10D64/62** (20250101); H01L21/0465 (20130101); H10D30/66 (20250101); H10D62/834 (20250101)

Field of Classification Search

CPC: H01L (21/0465); H01L (21/0485); H10D (12/031); H10D (12/441); H10D (30/66); H10D (62/8325); H10D (62/834); H10D (64/01); H10D (64/62)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5622743	12/1996	Tanaka et al.	N/A	N/A
6235616	12/2000	Itoh	257/E21.057	H01L 21/046
10062759	12/2017	Hisamoto et al.	N/A	N/A
10700167	12/2019	Kitamura et al.	N/A	N/A
2002/0182845	12/2001	Miyano et al.	N/A	N/A
2003/0068582	12/2002	Komada et al.	N/A	N/A
2012/0214309	12/2011	Itoh	156/345.31	H01L 21/049
2013/0062623	12/2012	Shimizu et al.	N/A	N/A
2018/0308936	12/2017	Shimizu	N/A	H10D 62/8325
2021/0288158	12/2020	Shimizu	N/A	N/A
2022/0005925	12/2021	Shimizu et al.	N/A	N/A
2022/0028688	12/2021	Sakai et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
8-66176	12/1995	JP	N/A
2002-359241	12/2001	JP	N/A
2003-124189	12/2002	JP	N/A
2008-227319	12/2007	JP	N/A
2013-58668	12/2012	JP	N/A
2014-143248	12/2013	JP	N/A
2016-46309	12/2015	JP	N/A
2018-98227	12/2017	JP	N/A
2018-186125	12/2017	JP	N/A
2021-145112	12/2020	JP	N/A
2022-12282	12/2021	JP	N/A
2022-20995	12/2021	JP	N/A
WO 2014/155651	12/2013	WO	N/A

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This application is based upon and claims the benefit of priority from Japanese Patent Application No. 2022-041805, filed on Mar. 16, 2022, the entire contents of which are incorporated herein by reference.

FIELD

(2) Embodiments described herein relate generally to a method for manufacturing a semiconductor device, a semiconductor device, an inverter circuit, a driving device, a vehicle, and an elevator.

BACKGROUND

(3) Silicon carbide (SiC) is expected as a material for next-generation semiconductor devices. As compared with silicon (Si), silicon carbide is excellent in physical properties, for example, about three times the band gap, about ten times the breakdown field strength, and about three times the thermal conductivity. By utilizing these physical properties, a semiconductor device capable of performing low-loss operation and operating at a high temperature can be realized.

(4) In a device using the silicon carbide, it is desired to reduce contact resistance between a silicon carbide layer and a metal electrode in order to improve a device property.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a schematic cross-sectional view of a semiconductor device manufactured by a method for manufacturing a semiconductor device according to a first embodiment;

(2) FIG. 2 is a flow chart illustrating a method for manufacturing a semiconductor device according to the first embodiment;

(3) FIG. 3 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(4) FIG. 4 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(5) FIG. 5 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(6) FIG. 6 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(7) FIG. 7 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(8) FIG. 8 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(9) FIG. 9 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(10) FIG. 10 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(11) FIG. 11 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(12) FIG. 12 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(13) FIG. 13 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(14) FIG. 14 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(15) FIG. 15 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(16) FIG. 16 is an explanatory diagram of a method for manufacturing a semiconductor device according to the first embodiment;

(17) FIGS. 17A and 17B are diagrams illustrating a function and an effect of a method for manufacturing a semiconductor device according to the first embodiment;

(18) FIGS. 18A and 18B are diagrams illustrating a function and an effect of a method for manufacturing a semiconductor device according to the first embodiment;

(19) FIG. 19 is an explanatory diagram of a function and an effect of a method for manufacturing a semiconductor device according to the first embodiment;

(20) FIG. 20 is a schematic cross-sectional view of a semiconductor device according to a second embodiment;

(21) FIG. 21 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(22) FIG. 22 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(23) FIG. 23 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(24) FIG. 24 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(25) FIG. 25 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(26) FIG. 26 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(27) FIG. 27 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(28) FIG. 28 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(29) FIG. 29 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(30) FIG. 30 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(31) FIG. 31 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(32) FIG. 32 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(33) FIG. 33 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(34) FIG. 34 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(35) FIG. 35 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

(36) FIG. 36 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;

- (37) FIG. 37 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (38) FIG. 38 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (39) FIG. 39 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (40) FIG. 40 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (41) FIG. 41 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (42) FIG. 42 is a schematic cross-sectional view illustrating a method for manufacturing a semiconductor device according to the second embodiment;
- (43) FIG. 43 is a schematic view of a driving device according to a third embodiment;
- (44) FIG. 44 is a schematic view of a vehicle according to a fourth embodiment;
- (45) FIG. 45 is a schematic view of a vehicle according to a fifth embodiment; and
- (46) FIG. 46 is a schematic view of an elevator according to a sixth embodiment.

DETAILED DESCRIPTION

(47) A method for manufacturing a semiconductor device according to the embodiment includes: performing first ion implantation of ion-implanting a p-type impurity into a silicon carbide layer in a first projected range and by a first dose amount; performing second ion implantation of ion-implanting carbon (C) into the silicon carbide layer in a second projected range and by a second dose amount; performing a first heat treatment for activating the p-type impurity; performing a first oxidation treatment of oxidizing the silicon carbide layer; performing an etching treatment of etching the silicon carbide layer in an atmosphere containing hydrogen gas; forming, on the silicon carbide layer, a first metal film containing at least one metal element selected from a group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr); performing a second heat treatment for causing the silicon carbide layer to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming, on the silicon carbide layer, a second metal film having a chemical composition different from a chemical composition of the first metal film.

(48) Hereinafter, embodiments of the present disclosure will be described with reference to the drawings. In the following description, the same or similar members are denoted by the same reference numerals, and the description of the members described once is appropriately omitted.

(49) In the following description, in a case where notations of n.sup.+, n, and n.sup.-, and notations of p.sup.+, p, and p.sup.- are used, these notations represent the relative level of impurity concentration in each conductivity type. That is, it is indicated that n.sup.+ has n-type impurity concentration relatively higher than that of n, and n.sup.- has the n-type impurity concentration relatively lower than that of n. It is indicated that p.sup.+ has p-type impurity concentration relatively higher than that of p, and p.sup.- has the p-type impurity concentration relatively lower than that of p. n.sup.+ -type and n.sup.- -type may be simply referred to as n-type, and p.sup.+ -type and p.sup.- -type may be simply referred to as p-type. Unless otherwise specified, the impurity concentration of each region is represented by, for example, a value of the impurity concentration in the central portion of each region.

(50) The impurity concentration can be measured by, for example, secondary ion mass spectrometry (SIMS). The relative level of the impurity concentration can also be determined based on the level of carrier concentration obtained by, for example, scanning capacitance microscopy (SCM). A distance such as the width and depth of an impurity region can be obtained by, for example, the SIMS. The distance such as the width and depth of an impurity region can be obtained from, for example, an SCM image.

(51) The thickness or the like of an insulating layer can be measured, for example, by using images

of the SIMS or a transmission electron microscope (TEM).

(52) The magnitude relationship among a ratio of a metal element in a silicon carbide layer, which is located at a silicon site in a crystal structure of silicon carbide, a ratio of the metal element located at a carbon site in the crystal structure of the silicon carbide, and a ratio of the metal element located at the interstitial site in the crystal structure of the silicon carbide can be determined by using, for example, Raman spectroscopy or X-ray photoelectron spectroscopy (XPS).

(53) For identification of a silicide phase present in a metal silicide layer and determination of a magnitude relationship of the amount of the silicide phase present in the metal silicide layer, for example, X-ray photoelectron spectroscopy (XPS), infrared spectroscopy (Infrared Spectroscopy), or Raman spectroscopy is used.

First Embodiment

(54) A method for manufacturing a semiconductor device according to the first embodiment includes: performing first ion implantation of ion-implanting a p-type impurity into a silicon carbide layer in a first projected range and by a first dose amount; performing second ion implantation of ion-implanting carbon (C) into the silicon carbide layer in a second projected range and by a second dose amount; performing a first heat treatment for activating the p-type impurity; performing a first oxidation treatment of oxidizing the silicon carbide layer; performing an etching treatment of etching the silicon carbide layer in an atmosphere containing hydrogen gas; forming, on the silicon carbide layer, a first metal film containing at least one metal element selected from a group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr); performing a second heat treatment for causing the silicon carbide layer to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming, on the silicon carbide layer, a second metal film having a chemical composition different from a chemical composition of the first metal film.

(55) FIG. 1 is a schematic cross-sectional view of a semiconductor device manufactured by the method for manufacturing a semiconductor device according to the first embodiment. The semiconductor device of the first embodiment is a semiconductor device including a contact structure **100**.

(56) The contact structure **100** includes a silicon carbide layer **10**, a contact electrode **11**, a metal silicide layer **13**, and an insulating layer **15**.

(57) The silicon carbide layer **10** includes a p-type low-concentration region **16** and a p-type high-concentration region **17**.

(58) The silicon carbide layer **10** is, for example, a single crystal of 4H—SiC. The silicon carbide layer **10** has a first surface F1 and a second surface F2. The second surface F2 is opposed to the first surface F1. The first surface F1 is a surface of the silicon carbide layer **10**, and the second surface F2 is a back surface of the silicon carbide layer **10**.

(59) In the first embodiment, a “depth” means a depth with respect to the first surface F1. Here, the first surface F1 is a virtual plane surface including an interface between the silicon carbide layer **10** and the insulating layer **15**.

(60) Hereinafter, a case where the first surface F1 of the silicon carbide layer **10** is a surface inclined at equal to or greater than zero degrees and equal to or less than ten degrees with respect to a silicon face, and the second surface F2 is a surface inclined at equal to or greater than zero degrees and equal to or less than ten degrees with respect to a carbon face will be described as an example. The first surface F1 of the silicon carbide layer has an off angle of equal to or greater than zero degrees and equal to or less than ten degrees with respect to the silicon face.

(61) The p-type low-concentration region **16** is p-type SiC. The p-type low-concentration region **16** contains, for example, aluminum (Al) as a p-type impurity. The p-type impurity concentration of the p-type low-concentration region **16** is, for example, equal to or greater than $1 \times 10^{15} \text{ cm}^{-3}$ and equal to or less than $5 \times 10^{17} \text{ cm}^{-3}$.

(62) The p-type high-concentration region **17** is p⁺-type SiC. The p-type high-concentration region **17** is provided between the p-type low-concentration region **16** and the first surface **F1**.

(63) The p-type high-concentration region **17** contains, for example, aluminum (Al) as a p-type impurity. The p-type impurity concentration of the p-type high-concentration region **17** is higher than the p-type impurity concentration of the p-type low-concentration region **16**. The p-type impurity concentration of the p-type high-concentration region **17** is, for example, equal to or greater than $1 \times 10^{18} \text{ cm}^{-3}$ and equal to or less than $1 \times 10^{22} \text{ cm}^{-3}$.

(64) The p-type high-concentration region **17** contains at least one metal element (M) selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr). The concentration of the metal element (M) of the p-type high-concentration region **17** is, for example, equal to or greater than $1 \times 10^{18} \text{ cm}^{-3}$ and equal to or less than $1 \times 10^{21} \text{ cm}^{-3}$.

(65) Among the metal elements (M) contained in the p-type high-concentration region **17**, for example, a ratio of the metal element (M) located at the interstitial site in the crystal structure of the silicon carbide is higher than a ratio of the metal element (M) located at the carbon site in the crystal structure of the silicon carbide.

(66) The insulating layer **15** is formed on the silicon carbide layer **10**. The insulating layer **15** is formed of, for example, silicon oxide.

(67) The contact electrode **11** is located on the first surface **F1** side of the silicon carbide layer **10**. The contact electrode **11** is electrically connected to the p-type high-concentration region **17**. The contact electrode **11** is in contact with the metal silicide layer **13**.

(68) The contact electrode **11** contains metal. The contact electrode **11** is formed of, for example, aluminum, an aluminum alloy, tungsten, or copper.

(69) For example, a barrier metal film (not illustrated) may be provided between the contact electrode **11** and the metal silicide layer **13**. The barrier metal film is formed of, for example, titanium or titanium nitride.

(70) The metal silicide layer **13** is provided between the silicon carbide layer **10** and the contact electrode **11**. The metal silicide layer **13** is in contact with the silicon carbide layer **10**. The metal silicide layer **13** is in contact with the contact electrode **11**.

(71) The metal silicide layer **13** contains, for example, silicide of at least one metal element (M) selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr). The metal silicide layer **13** contains, for example, nickel silicide, palladium silicide, platinum silicide, or chromium silicide. The metal silicide layer **13** is formed of, for example, nickel silicide, palladium silicide, platinum silicide, or chromium silicide.

(72) The thickness of the metal silicide layer **13** in a normal direction of the first surface **F1** of the silicon carbide layer **10** is, for example, equal to or greater than 50 nm and equal to or less than 500 nm.

(73) Next, an example of the method for manufacturing a semiconductor device according to the first embodiment will be described.

(74) FIG. 2 is a flow chart illustrating the method for manufacturing a semiconductor device according to the first embodiment. FIGS. 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, and 16 are explanatory diagrams of the method for manufacturing a semiconductor device according to the first embodiment. FIGS. 3 to 5 and FIGS. 7 to 16 are cross-sectional views in the middle of manufacturing. FIG. 6 is a diagram illustrating an element distribution immediately after ion implantation.

(75) Hereinafter, a case where the metal element (M) is nickel (Ni) will be described as an example.

(76) As illustrated in FIG. 2, the method for manufacturing a semiconductor device includes silicon carbide layer preparation (step **S100**), ion implantation of aluminum (step **S101**), ion implantation of carbon (step **S102**), carbon film formation (step **S103**), activation annealing (step **S104**), carbon film removal (step **S105**), insulating layer formation (step **S106**), contact hole formation (step

S107), sacrificial oxidation (step S108), a hydrogen etching treatment (step S109), nickel film formation (step S110), silicidation annealing (step S111), unreacted nickel film removal (step S112), and aluminum film formation (step S113).

(77) In step S100, the silicon carbide layer **10** is prepared (FIG. 3). The silicon carbide layer **10** includes the p-type low-concentration region **16**. The silicon carbide layer **10** has a first surface F1 and a second surface F2.

(78) In step S101, aluminum (Al) as the p-type impurity is ion-implanted into the silicon carbide layer **10**. The p-type high-concentration region **17** is formed by the ion implantation (FIG. 4).

(79) The ion implantation of aluminum forming the p-type high-concentration region **17** is an example of a first ion implantation. The ion implantation of aluminum is performed in a first projected range and by a first dose amount. The projected range is an average projection range.

(80) The first projected range is, for example, equal to or greater than $0.05\text{ }\mu\text{m}$ and equal to or less than $0.2\text{ }\mu\text{m}$. The first dose amount is, for example, equal to or greater than $1\times 10^{15}\text{ cm}^{-2}$ and equal to or less than $1\times 10^{16}\text{ cm}^{-2}$.

(81) In step S102, carbon is ion-implanted into the p-type high-concentration region **17** (FIG. 5). The ion implantation of carbon into the p-type high-concentration region **17** is an example of a second ion implantation. The ion implantation of carbon is performed in a second projected range and by a second dose amount.

(82) The second projected range is, for example, equal to or greater than $0.05\text{ }\mu\text{m}$ and equal to or less than $0.2\text{ }\mu\text{m}$. The second projected range is, for example, equal to or greater than 80% and equal to or less than 120% of the first projected range.

(83) The second dose amount is, for example, greater than the first dose amount. The second dose amount is, for example, equal to or greater than ten times the first dose amount. The second dose amount is, for example, equal to or less than one hundred times the first dose amount. The second dose amount is, for example, equal to or greater than $1\times 10^{16}\text{ cm}^{-2}$ and equal to or less than $1\times 10^{18}\text{ cm}^{-2}$.

(84) FIG. 6 illustrates a concentration distribution of aluminum implanted into the silicon carbide layer **10** by the first ion implantation and a concentration distribution of carbon implanted into the silicon carbide layer **10** by the second ion implantation. FIG. 6 is a diagram illustrating an element distribution immediately after the ion implantation.

(85) As illustrated in FIG. 6, a second projected range Rp2 of the ion implantation of carbon is located in the vicinity of a first projected range Rp1 of the ion implantation of aluminum. Since the second dose amount of the ion implantation of carbon is greater than the first dose amount of the ion implantation of aluminum, the concentration distribution of carbon after the ion implantation completely covers, for example, the concentration distribution of aluminum after the ion implantation.

(86) The concentration at a peak of the distribution of aluminum is, for example, equal to or greater than $1\times 10^{19}\text{ cm}^{-3}$ and equal to or less than $1\times 10^{21}\text{ cm}^{-3}$. The concentration at a peak of the distribution of carbon is, for example, equal to or greater than $1\times 10^{20}\text{ cm}^{-3}$ and equal to or less than $1\times 10^{22}\text{ cm}^{-3}$.

(87) In step S103, a carbon film **60** is formed on the silicon carbide layer **10** (FIG. 7).

(88) In step S104, a first heat treatment is performed. The first heat treatment is activation annealing for activating ion-implanted aluminum.

(89) The first heat treatment is performed, for example, at equal to or higher than 1600°C . The first heat treatment is performed, for example, at equal to or lower than 2000°C . The first heat treatment is performed, for example, in a non-oxidizing atmosphere. The first heat treatment is performed, for example, in an inert gas atmosphere. The first heat treatment is performed, for example, in an argon gas atmosphere.

(90) By the first heat treatment, interstitial carbon formed by ion implantation of carbon into the silicon carbide layer **10** fills a carbon vacancy in the silicon carbide layer **10**.

(91) The carbon film **60** prevents silicon and carbon from being desorbed from the silicon carbide layer **10** into the atmosphere during the first heat treatment. The carbon film **60** absorbs excessive interstitial carbon in the silicon carbide layer **10** during the first heat treatment.

(92) The first heat treatment includes, for example, a first step in which a temperature is equal to or greater than 1600° C. and a second step in which a temperature is lower than that of the first step. In the second step, the temperature is, for example, equal to or lower than 1000° C.

(93) For example, in the first step, aluminum ion-implanted into the silicon carbide layer **10** is activated, and the interstitial carbon fills the carbon vacancy. For example, in the second step in which the temperature is low, excessive interstitial carbon is expelled from the silicon carbide layer **10** and absorbed by the carbon film **60**.

(94) In step **S105**, the carbon film **60** is removed (FIG. **8**). The carbon film **60** is removed by an ashing treatment using oxygen plasma. The carbon film **60** is removed in the oxygen plasma.

(95) During the ashing treatment using oxygen plasma, the surface of the silicon carbide layer **10** is oxidized. The ashing treatment using oxygen plasma is an example of a first oxidation treatment.

(96) In step **S106**, the insulating layer **15** is formed on the silicon carbide layer **10** (FIG. **9**). The insulating layer **15** is formed using, for example, a chemical vapor deposition method (CVD method). The insulating layer **15** is formed of, for example, silicon oxide.

(97) In step **S107**, a contact hole **61** is formed in the insulating layer **15** (FIG. **10**). The contact hole **61** is an example of an opening. The silicon carbide layer **10** is exposed at the bottom portion of the contact hole **61**. The p-type high-concentration region **17** is exposed at the bottom portion of the contact hole **61**.

(98) The contact hole **61** is formed by, for example, patterning using photolithography and etching.

(99) In step **S108**, the sacrificial oxidation of the silicon carbide layer **10** is performed. The sacrificial oxidation is thermal oxidation. A sacrificial oxide film **62** is formed on the silicon carbide layer **10** by sacrificial oxidation (FIG. **11**). The sacrificial oxidation is an example of a second oxidation treatment.

(100) The sacrificial oxide film **62** is a silicon oxide film. By forming the sacrificial oxide film **62**, for example, the impurity and damage on the surface of the silicon carbide layer **10** are removed.

(101) Next, the sacrificial oxide film **62** is removed. The sacrificial oxide film **62** is removed using, for example, a wet etching method.

(102) In step **S109**, the hydrogen etching treatment for etching the surface of the silicon carbide layer **10** in an atmosphere containing hydrogen gas is performed (FIG. **12**). The temperature of the hydrogen etching treatment is, for example, equal to or higher than 1300° C. and equal to or lower than 1500° C. The surface of the silicon carbide layer **10** is etched by, for example, equal to or greater than 25 nm and equal to or less than 100 nm by performing the hydrogen etching treatment.

(103) The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, equal to or greater than 90%. The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, equal to or greater than 95%. The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, 100%. The atmosphere of the hydrogen etching treatment may include, for example, argon gas.

(104) In step **S110**, a nickel film **48** is formed on the silicon carbide layer **10** (FIG. **13**). The nickel film **48** is an example of a first metal film. Nickel (Ni) is an example of a metal element. The nickel film **48** is formed using, for example, a sputtering method.

(105) In step **S111**, silicidation annealing is performed. A nickel silicide layer **50** is formed by causing the silicon carbide layer **10** to react with the nickel film **48** by silicidation annealing (FIG. **14**). The nickel silicide layer **50** is an example of the metal silicide layer **13**.

(106) The silicidation annealing is performed, for example, in an atmosphere containing nitrogen. The silicidation annealing is performed, for example, in an atmosphere containing nitrogen gas. The temperature of the silicidation annealing is, for example, equal to or higher than 500° C. and

lower than 900° C.

(107) At the time of silicidation annealing, the nickel is diffused from the nickel film **48** into the silicon carbide layer **10**. The nickel is diffused into the p-type high-concentration region **17** at the time of silicidation annealing.

(108) In step **S112**, an unreacted nickel film **48** is removed (FIG. **15**). The unreacted nickel film is removed by, for example, wet etching.

(109) Thereafter, in step **S113**, an aluminum film **51** is formed on the nickel silicide layer **50** (FIG. **16**). The aluminum film **51** is an example of a second metal film. The second metal film has a chemical composition different from that of the first metal film. The aluminum film **51** is formed by, for example, a sputtering method.

(110) The aluminum film **51** is patterned to finally become the contact electrode **11**.

(111) The contact structure **100** illustrated in FIG. **1** is formed by the manufacturing method described above.

(112) Next, a function and an effect of the method for manufacturing a semiconductor device according to the first embodiment will be described.

(113) In the method for manufacturing the contact structure **100** of the first embodiment, when the p-type high-concentration region **17** is formed, carbon is ion-implanted in addition to the ion implantation of aluminum. After the oxidation treatment, the surface of the p-type high-concentration region **17** is etched by the hydrogen etching treatment before the metal silicide layer **13** is formed. In the above-described method, the amount of carbon vacancies in the p-type high-concentration region **17** is reduced. Therefore, the contact resistance between the p-type high-concentration region **17** and the contact electrode **11** decreases. Details will be described below.

(114) In the semiconductor device using silicon carbide, from the viewpoint of improving the property of the semiconductor device, it is desirable to reduce the contact resistance between the p-type impurity region and the electrode and the contact resistance between the n-type impurity region and the electrode.

(115) In the contact structure **100**, the metal silicide layer **13** is provided between the p-type high-concentration region **17** and the contact electrode **11**. By using the metal silicide layer **13**, the contact resistance between the p-type high-concentration region **17** and the contact electrode **11** decreases.

(116) In general, it is known that the contact resistance between an n-type silicon carbide region and the metal silicide layer decreases as the temperature of silicidation annealing increases. On the other hand, it is known that the contact resistance between a p-type silicon carbide region and the metal silicide layer increases as the temperature of silicidation annealing increases.

(117) Therefore, it is difficult to simultaneously reduce both the contact resistance between the n-type silicon carbide region and the electrode, and the contact resistance between the p-type silicon carbide region and the electrode.

(118) In a case where the metal element (M) contained in the metal silicide layer is one selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr), the following facts have been revealed as a result of the first principle calculation by the inventor.

(119) That is, it has been revealed that the metal element (M) easily enters the carbon site in the crystal structure of silicon carbide at a high temperature of equal to or higher than 900° C., and easily enters the interstitial site of the crystal structure of the silicon carbide at a low temperature of lower than 900° C. It has been revealed that the metal element (M) entering the carbon site functions as a donor, and the metal element (M) entering the interstitial site functions as an acceptor.

(120) FIGS. **17A**, **17B**, **18A**, and **18B** are diagrams illustrating a function and an effect of the method for manufacturing a semiconductor device according to the first embodiment. FIGS. **17A**, **17B**, **18A**, and **18B** are band diagrams of silicon carbide.

(121) FIGS. **17A** and **17B** are explanatory diagrams in a case where the metal element (M) enters

the carbon site in the crystal structure of the silicon carbide. FIG. 17A illustrates a case where the metal element (M) is not present in the silicon carbide layer, and FIG. 17B illustrates a case where the metal element (M) is present in the silicon carbide layer.

(122) As illustrated in FIG. 17B, in a case where the metal element (M) enters the carbon site in the crystal structure of the silicon carbide, a donor level due to the metal element (M) is formed at a lower end of a conduction band, and electrons are supplied to the conduction band. The metal element (M) functions as a donor.

(123) FIGS. 18A and 18B are explanatory diagrams in a case where the metal element (M) enters the interstitial site of the crystal structure of the silicon carbide. FIG. 18A illustrates a case where the metal element (M) is not present in the silicon carbide layer, and FIG. 18B illustrates a case where the metal element (M) is present in the silicon carbide layer.

(124) As illustrated in FIG. 18B, in a case where the metal element (M) enters the interstitial site of the crystal structure of the silicon carbide, an acceptor level due to the metal element (M) is formed at an upper end of a valence band, electrons are supplied to the acceptor level, and holes are formed at the valence band. The metal element (M) functions as an acceptor.

(125) From the calculation result described above, the reason why the contact resistance between the n-type silicon carbide region and the metal silicide layer decreases as the temperature of the silicidation annealing increases is considered as below. That is, when the temperature of the silicidation annealing is high, the metal element diffused from the metal film into the n-type silicon carbide region at the time of forming the metal silicide layer enters the carbon site in the crystal structure of the silicon carbide and becomes a donor. Therefore, the donor concentration of the n-type silicon carbide region increases. Accordingly, a Schottky barrier between the n-type silicon carbide region and the metal silicide layer is lowered, a tunnel current easily flows, and the contact resistance decreases.

(126) From the calculation result described above, the reason why the contact resistance between the p-type silicon carbide region and the metal silicide layer increases as the temperature of the silicidation annealing increases is considered as below. That is, when the temperature of the silicidation annealing is high, the metal element diffused from the metal film into the p-type silicon carbide region at the time of forming the metal silicide layer enters the carbon site in the crystal structure of the silicon carbide and becomes a donor. For this reason, the acceptor concentration of the p-type silicon carbide region is offset and becomes low. Accordingly, the Schottky barrier between the p-type silicon carbide region and the metal silicide layer rises, the tunnel current hardly flows, and the contact resistance increases.

(127) In the method for manufacturing the contact structure **100** of the first embodiment, when the p-type high-concentration region **17** is formed, carbon (C) is ion-implanted in addition to the ion implantation of aluminum (Al). Due to the ion implantation of the carbon (C), a large amount of excessive interstitial carbons are present in the p-type high-concentration region **17**. Due to the heat treatment performed after the ion implantation of the carbon, the carbon vacancies generated by the ion implantation of aluminum are filled with the excessive interstitial carbons. Therefore, the amount of carbon vacancies in the p-type high-concentration region **17** is reduced. Therefore, the metal element (M) of the p-type high-concentration region **17** easily enters the interstitial site of the crystal structure of the silicon carbide. Accordingly, the acceptor concentration of the p-type high-concentration region **17** increases.

(128) From the viewpoint of reducing the amount of carbon vacancies in the p-type high-concentration region **17**, the second dose amount of carbon is preferably equal to or greater than 10 times the first dose amount of aluminum.

(129) From the viewpoint of reducing the amount of carbon vacancies in the p-type high-concentration region **17**, the second projected range Rp2 of the ion implantation of carbon is preferably equal to or greater than 80% and equal to or less than 120% of the first projected range Rp1 of the ion implantation of aluminum, and more preferably equal to or greater than 90% and

equal to or less than 110% of the first projected range Rp1 of the ion implantation of aluminum.

(130) When the first projected range Rp1 and the second projected range Rp2 are brought close to each other, the concentration distribution of carbon after the ion implantation completely and easily cover the concentration distribution of aluminum after the ion implantation. When the concentration distribution of carbon after the ion implantation completely covers the concentration distribution of aluminum after the ion implantation, the amount of carbon vacancies in the p-type high-concentration region 17 is reduced.

(131) FIG. 19 is an explanatory diagram of a function and an effect of the method for manufacturing a semiconductor device according to the first embodiment. FIG. 19 is a diagram illustrating a relationship between the depth from a silicon carbide layer surface and a carbon vacancy density.

(132) As illustrated in FIG. 19, in a case where ion implantation of carbon is performed in addition to the ion implantation of aluminum, the carbon vacancy density can be kept low at equal to or less than $1 \times 10^{11} \text{ cm}^{-3}$ when the silicon carbide layer is not subjected to the oxidation treatment. However, in a case where the oxidation treatment is performed after the ion implantation, for example, the carbon vacancy density increases up to a region of 25 nm from the silicon carbide layer surface. It is considered that the reason why the carbon vacancy density increases is that the carbon vacancies are generated due to a distortion generated on the silicon carbide layer surface by the oxidation treatment.

(133) As illustrated in FIG. 19, in a case where the ion implantation of carbon is not performed in addition to the ion implantation of aluminum, when the oxidation treatment is performed after the ion implantation, for example, the carbon vacancy density increases up to a region of 200 nm from the silicon carbide layer surface. In a case where the ion implantation of carbon is not performed, ion implantation damage of aluminum remains, and the carbon vacancy density of the silicon carbide layer before the oxidation treatment is as high as about $1 \times 10^{14} \text{ cm}^{-3}$. Therefore, diffusion of oxygen through the carbon vacancies is promoted, and the distortion of silicon carbide occurs up to a deep region of the silicon carbide layer.

(134) In the method for manufacturing the contact structure 100 according to the first embodiment, after the silicon carbide layer 10 is subjected to the oxidation treatment, the surface of the silicon carbide layer 10 is etched by the hydrogen etching treatment. The oxidation treatment is, for example, an ashing treatment using oxygen plasma for removing the carbon film 60, and a thermal oxidation treatment for forming the sacrificial oxide film 62. In particular, it is difficult to omit the ashing treatment using oxygen plasma for removing the carbon film 60 from the viewpoint of suppressing desorption of silicon and carbon from the silicon carbide layer 10 into the atmosphere during the first heat treatment.

(135) The hydrogen etching treatment removes a region having a high carbon vacancy density, and thus the carbon vacancy density on the surface of the silicon carbide layer is reduced. Therefore, the amount of carbon vacancies in the p-type high-concentration region 17 immediately below the nickel silicide layer is reduced.

(136) Therefore, when the nickel silicide layer is formed, the metal element (M) of the p-type high-concentration region 17 easily enters the interstitial site of the crystal structure of the silicon carbide. Accordingly, the acceptor concentration of the p-type high-concentration region 17 increases.

(137) From the viewpoint of reducing the carbon vacancy density of the surface of the silicon carbide layer 10, the etching amount of the surface of the silicon carbide layer at the time of the hydrogen etching treatment is preferably equal to or greater than 25 nm.

(138) From the viewpoint of increasing the acceptor concentration of the p-type high-concentration region 17, the temperature of the silicidation annealing is preferably lower than 900°C .

(139) According to the method for manufacturing the contact structure 100 of the first embodiment, the contact resistance between the p-type high-concentration region 17 and the contact electrode 11

decreases.

(140) It is also possible to remove the nickel silicide layer after forming the nickel silicide layer and before forming the aluminum film **51**. In this case, the aluminum film **51** is in contact with the p-type high-concentration region **17**.

(141) In the method for manufacturing the contact structure **100** of the first embodiment, the acceptor concentration of the p-type high-concentration region **17** can be increased. Therefore, even in a case where the aluminum film **51** is in contact with the p-type high-concentration region **17**, the contact resistance between the p-type high-concentration region **17** and the contact electrode **11** can be reduced.

(142) As described above, according to the first embodiment, it is possible to realize a semiconductor device capable of reducing the contact resistance between the silicon carbide layer and the metal electrode.

Second Embodiment

(143) A method for manufacturing a semiconductor device according the second embodiment includes: performing first ion implantation of ion-implanting a p-type impurity into a first region of a silicon carbide layer; performing second ion implantation of ion-implanting carbon (C) into the first region; performing a third ion implantation of ion-implanting an n-type impurity into a second region of the silicon carbide layer; performing a first heat treatment for activating the n-type impurity and the p-type impurity; forming a gate insulating layer on the silicon carbide layer; forming a gate electrode on the gate insulating layer; performing an etching treatment of etching at least the first region in an atmosphere containing hydrogen gas after the gate electrode is formed; forming, on the first region and the second region, a first metal film containing at least one metal element selected from a group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr); performing a second heat treatment for causing the first region and second region to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming, on the first region and the second region, a second metal film having a chemical composition different from a chemical composition of the first metal film. The method for manufacturing a semiconductor device according to the second embodiment is different from that of the first embodiment in that an n-type impurity is ion-implanted into a second region of the silicon carbide layer to form a metal silicide layer in the second region. Hereinafter, description of the contents overlapping with the first embodiment may be partially omitted.

(144) A semiconductor device according to the second embodiment includes: a silicon carbide layer including a p-type first silicon carbide region containing at least one metal element selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr) and an n-type second silicon carbide region containing a metal element; and a metal layer electrically connected to the first silicon carbide region and the second silicon carbide region. A ratio of intensity of infrared absorption at a wave number of 838 cm^{-1} with respect to the intensity of the infrared absorption at a wave number of 970 cm^{-1} , which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), is a first value in the vicinity of the surface of the first silicon carbide region, and the ratio is a second value greater than the first value in the vicinity of the surface of the second silicon carbide region.

(145) FIG. **20** is a schematic cross-sectional view of the semiconductor device according to the second embodiment. The semiconductor device of the second embodiment is a vertical MOSFET **200**. The MOSFET **200** is an n-channel transistor using electrons as a carrier.

(146) The MOSFET **200** includes a silicon carbide layer **10**, a source electrode **12** (metal layer), a metal silicide layer **13** (conductive layer), a drain electrode **14**, a gate insulating layer **18**, a gate electrode **20**, and an interlayer insulating layer **22**.

(147) The source electrode **12** is an example of the metal layer. The metal silicide layer **13** is an example of the conductive layer.

(148) The silicon carbide layer **10** includes a drain region **24**, a drift region **26**, a p-well region **28**, a source region **30** (second silicon carbide region), and a p-well contact region **32** (first silicon carbide region).

(149) The silicon carbide layer **10** is, for example, a single crystal of 4H—SiC. The silicon carbide layer **10** has a first surface **F1** and a second surface **F2**. The second surface **F2** is opposed to the first surface **F1**. The first surface **F1** is a surface of the silicon carbide layer **10**, and the second surface **F2** is a back surface of the silicon carbide layer **10**.

(150) In the second embodiment, a “depth” means a depth with respect to the first surface **F1**. Here, the first surface **F1** is a virtual plane surface including an interface between the silicon carbide layer **10** and the gate insulating layer **18**.

(151) Hereinafter, a case where the first surface **F1** of the silicon carbide layer **10** is a surface inclined at equal to or greater than zero degrees and equal to or less than ten degrees with respect to a silicon face, and the second surface **F2** is a surface inclined at equal to or greater than zero degrees and equal to or less than ten degrees with respect to a carbon face will be described as an example. The first surface **F1** of the silicon carbide layer has an off angle of equal to or greater than zero degrees and equal to or less than ten degrees with respect to the silicon face.

(152) The drain region **24** is n.sup.+ -type SiC. The drain region **24** contains, for example, nitrogen (N) as an n-type impurity. The n-type impurity concentration of the drain region **24** is, for example, equal to or greater than 1×10^{18} cm.sup.-3 and equal to or less than 1×10^{21} cm.sup.-3.

(153) The drift region **26** is n.sup.- -type SiC. The drift region **26** is located between the drain region **24** and the first surface **F1**. A part of the drift region **26** is in contact with the first surface **F1**.

(154) The drift region **26** contains, for example, nitrogen (N) as an n-type impurity. The n-type impurity concentration of the drift region **26** is, for example, equal to or greater than 1×10^{15} cm.sup.-3 and equal to or less than 2×10^{16} cm.sup.-3. The n-type impurity concentration of the drift region **26** is lower than the n-type impurity concentration of the drain region **24**.

(155) The drift region **26** is, for example, a Sic epitaxial growth layer formed on the drain region **24** by epitaxial growth. The thickness of the drift region **26** is, for example, equal to or greater than 5 μ m and equal to or less than 100 μ m.

(156) The p-well region **28** is p-type SiC. The p-well region **28** is located between the drift region **26** and the first surface **F1**. A part of the p-well region **28** is in contact with the first surface **F1**.

(157) The p-well region **28** contains, for example, aluminum (Al) as a p-type impurity. The p-type impurity concentration of the p-well region **28** is, for example, equal to or greater than 1×10^{16} cm.sup.-3 and equal to or less than 1×10^{20} cm.sup.-2.

(158) The depth of the p-well region **28** is, for example, equal to or greater than 0.4 μ m and equal to or less than 0.8 μ m. The p-well region **28** functions as a channel region of the MOSFET **200**.

(159) The source region **30** is n.sup.+ -type SiC. The source region **30** is located between the p-well region **28** and the first surface **F1**. A part of the source region **30** is in contact with the first surface **F1**. The source region **30** extends in a first direction.

(160) The source region **30** contains phosphorus (P) or nitrogen (N) as an n-type impurity. The n-type impurity concentration of the source region **30** is, for example, equal to or greater than 1×10^{18} cm.sup.-3 and equal to or less than 1×10^{22} cm.sup.-2. The n-type impurity concentration of the source region **30** is higher than the n-type impurity concentration of the drift region **26**.

(161) The depth of the source region **30** is smaller than the depth of the p-well region **28**. The depth of the source region **30** is, for example, equal to or greater than 0.1 μ m and equal to or less than 0.4 μ m.

(162) The source region **30** contains at least one metal element (M) selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr). The concentration of the metal element (M) of the source region **30** is, for example, equal to or greater than 1×10^{18} cm.sup.-3 and equal to or less than 1×10^{21} cm.sup.-3.

(163) Among the metal elements (M) contained in the source region **30**, a ratio of the metal element (M) located at the carbon site in the crystal structure of the silicon carbide is higher than a ratio of the metal element (M) located at the interstitial site of the crystal structure of the silicon carbide. It is preferable that 90% or greater of the metal elements (M) contained in the source region **30** is located at the carbon site in the crystal structure of the silicon carbide. It is possible to realize the structure described above by devising to increase the number of carbon vacancies.

(164) The p-well contact region **32** is p.sup.+ -type SiC. The p-well contact region **32** is located between the p-well region **28** and the first surface F1. The p-well contact region **32** is adjacent to the source region **30**. The p-well contact region **32** is in contact with the source region **30**.

(165) The p-well contact region **32** contains, for example, aluminum as a p-type impurity. The p-type impurity concentration of the p-well contact region **32** is, for example, equal to or greater than $1 \times 10^{18} \text{ cm}^{-3}$ and equal to or less than $1 \times 10^{22} \text{ cm}^{-3}$. The p-type impurity concentration of the p-well contact region **32** is higher than the p-type impurity concentration of the p-well region **28**.

(166) The depth of the p-well contact region **32** is smaller than the depth of the p-well region **28**. The depth of the p-well contact region **32** is, for example, equal to or greater than $0.1 \mu\text{m}$ and equal to or less than $0.4 \mu\text{m}$.

(167) The p-well contact region **32** contains at least one metal element (M) selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr). The concentration of the metal element (M) of the p-well contact region **32** is, for example, equal to or greater than $1 \times 10^{10} \text{ cm}^{-3}$ and equal to or less than $1 \times 10^{21} \text{ cm}^{-3}$.

(168) Among the metal elements (M) contained in the p-well contact region **32**, a ratio of the metal element (M) located at the interstitial site of the crystal structure of the silicon carbide is higher than a ratio of the metal element (M) located at the carbon site in the crystal structure of the silicon carbide. It is preferable that 90% or greater of the metal elements (M) contained in the p-well contact region **32** is located at the interstitial site of the crystal structure of the silicon carbide. It is possible to realize the structure described above by devising to decrease the number of carbon vacancies.

(169) A ratio of intensity of infrared absorption at a wave number of 838 cm^{-1} with respect to the intensity of the infrared absorption at a wave number of 970 cm^{-1} , which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), is a first value in the vicinity of the surface of the p-well contact region **32**. The ratio of intensity of infrared absorption at a wave number of 838 cm^{-1} with respect to the intensity of the infrared absorption at a wave number of 970 cm^{-1} , which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), is a second value in the vicinity of the surface of the source region **30**.

(170) The second value is higher than the first value. The second value is, for example, equal to or greater than two times the first value.

(171) The gate insulating layer **18** is located between the silicon carbide layer **10** and the gate electrode **20**. The gate insulating layer **18** is located between the p-well region **28** and the gate electrode **20**.

(172) The gate insulating layer **18** is formed of, for example, an oxide or an oxynitride. The gate insulating layer **18** is formed of, for example, silicon oxide. The thickness of the gate insulating layer **18** is, for example, equal to or greater than 30 nm and equal to or less than 100 nm .

(173) The gate insulating layer **18** and the p-well region **28** are in contact with each other. The p-well region **28** in the vicinity of the gate insulating layer **18** is the channel region of the MOSFET **200**.

(174) The gate electrode **20** is located on the first surface F1 side of the silicon carbide layer **10**. The gate electrode **20** is provided on the gate insulating layer **18**. The gate electrode **20** sandwiches the gate insulating layer **18** with the drift region **26**, the source region **30**, and the p-well region **28**.

(175) The gate electrode **20** is formed of a conductor. The gate electrode **20** is formed of, for example, polycrystalline silicon containing an n-type impurity or a p-type impurity. The gate electrode **20** may be formed of, for example, metal such as titanium nitride, tungsten nitride, tungsten, aluminum, copper, ruthenium, cobalt, nickel, cobalt silicide, or nickel silicide. The gate electrode **20** may have a stacked structure obtained by stacking any one of the above-described metals and the polycrystalline silicon containing the n-type impurity or the p-type impurity.

(176) The interlayer insulating layer **22** is provided on the gate electrode **20**. The interlayer insulating layer **22** electrically isolates the gate electrode **20** from the source electrode **12**. The interlayer insulating layer **22** is formed of, for example, silicon oxide.

(177) The source electrode **12** is located on the first surface **F1** side of the silicon carbide layer **10**. The source electrode **12** is electrically connected to the source region **30** and the p-well contact region **32**. The source electrode **12** also functions as a p-well electrode that applies an electric potential to the p-well region **28**. The source electrode **12** is in contact with the metal silicide layer **13**.

(178) The source electrode **12** contains metal. The source electrode **12** is formed of, for example, aluminum, an aluminum alloy, tungsten, or copper.

(179) For example, a barrier metal film (not illustrated) may be provided between the source electrode **12** and the metal silicide layer **13**. The barrier metal film is formed of, for example, titanium or titanium nitride.

(180) The metal silicide layer **13** is provided between the silicon carbide layer **10** and the source electrode **12**. The metal silicide layer **13** is an example of the conductive layer. The metal silicide layer **13** is in contact with the silicon carbide layer **10**. The metal silicide layer **13** is in contact with the source electrode **12**.

(181) The metal silicide layer **13** contains, for example, silicide of at least one metal element (M) selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr). The metal silicide layer **13** contains, for example, nickel silicide, palladium silicide, platinum silicide, or chromium silicide. The metal silicide layer **13** is formed of, for example, nickel silicide, palladium silicide, platinum silicide, or chromium silicide.

(182) The thickness of the metal silicide layer **13** in a normal direction of the first surface **F1** of the silicon carbide layer **10** is, for example, equal to or greater than 50 nm and equal to or less than 500 nm.

(183) The drain electrode **14** is located on the second surface **F2** side of the silicon carbide layer **10**. The drain electrode **14** is in contact with the drain region **24**. The drain electrode **14** is electrically connected to the drain region **24**.

(184) The drain electrode **14** is formed of, for example, nickel. The nickel may react with the silicon carbide layer **10** to form nickel silicide. The nickel silicide is, for example, NiSi or Ni₃Si₂.

(185) Next, an example of the method for manufacturing a semiconductor device according to the second embodiment will be described.

(186) FIGS. **21**, **22**, **23**, **24**, **25**, **26**, **27**, **28**, **29**, **30**, **31**, **32**, **33**, **34**, **35**, **36**, **37**, **38**, **39**, **40**, **41**, and **42** are schematic cross-sectional views illustrating the method for manufacturing a semiconductor device of the second embodiment. FIGS. **21** to **42** are cross sections corresponding to FIG. **20**.

(187) First, the silicon carbide layer **10** is prepared (FIG. **21**). The silicon carbide layer **10** includes an n.sup.+ -type drain region **24** and an n.sup.- -type drift region **26**. For example, the drift region **26** is formed on the n.sup.- -type drain region **24** by an epitaxial growth method. The silicon carbide layer **10** has a first surface **F1** and a second surface **F2**.

(188) Next, a first mask material **40** formed of silicon oxide is formed by patterning by photolithography and etching. Next, by using the first mask material **40** as an ion implantation mask, aluminum (Al) as a p-type impurity is ion-implanted into the drift region **26** to form the p-well region **28** (FIG. **22**).

(189) Next, carbon (C) is ion-implanted into the p-well region **28** by using the first mask material **40** as the ion implantation mask (FIG. **23**). The ion implantation of carbon into the p-well region **28** reduces carbon vacancies in the p-well region **28**. By the ion implantation of carbon, the carbon vacancies in the p-well region **28** are filled with carbon, and the carbon vacancies are reduced.

(190) Next, a second mask material **42** formed of silicon oxide is formed by patterning by photolithography and etching. By using the second mask material **42** as an ion implantation mask, aluminum (Al) is ion-implanted into the p-well region **28** to form the p-well contact region **32** (FIG. **24**).

(191) A region in which the p-well contact region **32** is formed is an example of a first region. The ion implantation for forming the p-well contact region **32** is an example of the first ion implantation.

(192) Next, carbon (C) is ion-implanted into the p-well contact region **32** by using the second mask material **42** as the ion implantation mask (FIG. **25**). By the ion implantation of carbon into the p-well contact region **32**, the carbon vacancies in a second region are reduced. By the ion implantation of carbon, the carbon vacancies in the p-well contact region **32** are filled with carbon, and the carbon vacancies are reduced.

(193) The ion implantation of carbon into the p-well contact region **32** is an example of the second ion implantation.

(194) Next, a third mask material **44** formed of silicon oxide is formed by patterning by photolithography and etching. By using the third mask material **44** as an ion implantation mask, phosphorus (P) as an n-type impurity is ion-implanted into the p-well region **28** to form the source region **30** (FIG. **26**).

(195) A region in which the source region **30** is formed is an example of the second region. The ion implantation for forming the source region **30** is an example of the third ion implantation.

(196) Next, argon (Ar) is ion-implanted into the source region **30** by using the third mask material **44** as the ion implantation mask (FIG. **27**). The ion implantation of argon into the source region **30** increases carbon vacancies in the source region **30**. By the ion implantation of argon, the bond with the silicon carbide in the source region **30** is broken, and the carbon vacancies in the source region **30** increase.

(197) Next, the carbon film **60** is formed on the silicon carbide layer **10** (FIG. **28**).

(198) Next, the first heat treatment is performed. The first heat treatment is activation annealing for activating ion-implanted aluminum. The p-type impurities of the p-well region **28** and p-well contact region **32** and the n-type impurity of the source region **30** are activated.

(199) The first heat treatment is performed, for example, at equal to or higher than 1600° C. The first heat treatment is performed, for example, at equal to or lower than 2000° C. The first heat treatment is performed in a non-oxidizing atmosphere. The first heat treatment is performed, for example, in an inert gas atmosphere. The first heat treatment is performed, for example, in an argon gas atmosphere.

(200) By the first heat treatment, interstitial carbon formed by ion implantation of carbon into the silicon carbide layer **10** fills a carbon vacancy in the silicon carbide layer **10**.

(201) Next, the carbon film **60** is removed (FIG. **29**). The carbon film **60** is removed by an ashing treatment using oxygen plasma. The carbon film **60** is removed in the oxygen plasma. During the ashing treatment using oxygen plasma, the surface of the silicon carbide layer **10** is oxidized. The ashing treatment using oxygen plasma is an example of the oxidation treatment.

(202) Next, a field oxide film **65** is formed on the silicon carbide layer **10** (FIG. **30**). The field oxide film **65** contains oxygen. The field oxide film **65** is, for example, a silicon oxide film. The field oxide film **65** is deposited by, for example, a vapor phase growth method. The field oxide film **65** is formed by, for example, a CVD method or a physical vapor deposition method (PVD method).

(203) When the field oxide film **65** is deposited, the surface of the silicon carbide layer **10** is

oxidized. The deposition process of depositing the field oxide film **65** is an example of the oxidation treatment. The field oxide film **65** functions as, for example, an element isolation region in a peripheral region (not illustrated).

(204) Next, the field oxide film **65** is removed. The field oxide film **65** is removed using, for example, a wet etching method.

(205) Next, a sacrificial oxide film **66** is formed on the silicon carbide layer **10** (FIG. **31**). The sacrificial oxide film **66** is, for example, a silicon oxide film. The sacrificial oxide film **66** is formed by thermal oxidation of the surface of the silicon carbide layer **10**.

(206) When the sacrificial oxide film **66** is formed, the surface of the silicon carbide layer **10** is oxidized. The thermal oxidation treatment for forming the sacrificial oxide film **66** is an example of the oxidation treatment. By forming the sacrificial oxide film **66**, for example, the impurity and damage on the surface of the silicon carbide layer **10** are removed.

(207) Next, the sacrificial oxide film **66** is removed. The sacrificial oxide film **66** is removed using, for example, a wet etching method.

(208) Next, the gate insulating layer **18** is formed on the silicon carbide layer **10** by a CVD method or a thermal oxidation method. The gate insulating layer **18** is formed of, for example, silicon oxide. When the gate insulating layer **18** is formed, the surface of the silicon carbide layer **10** is oxidized. The process of forming the gate insulating layer **18** is an example of the oxidation treatment.

(209) Next, the gate electrode **20** is formed on the gate insulating layer **18** (FIG. **32**). The gate electrode **20** is formed of, for example, polycrystalline silicon. The gate electrode **20** is formed by, for example, deposition of a film by a CVD method and patterning by photolithography and etching.

(210) Next, an insulating layer **67** is formed on the gate electrode **20** (FIG. **33**). A part of the insulating layer **67** finally becomes the interlayer insulating layer **22**. The insulating layer **67** is formed of, for example, silicon oxide. The insulating layer **67** is formed by, for example, a CVD method.

(211) Next, the contact hole **61** is formed in the insulating layer **67** (FIG. **34**). The contact hole **61** is an example of an opening. The silicon carbide layer **10** is exposed at the bottom portion of the contact hole **61**. The p-well contact region **32** and the source region **30** are exposed at the bottom portion of the contact hole **61**.

(212) The contact hole **61** is formed by, for example, patterning by photolithography and etching.

(213) Next, the sacrificial oxidation of the silicon carbide layer **10** is performed. The sacrificial oxidation is thermal oxidation. A sacrificial oxide film **62** is formed on the silicon carbide layer **10** by sacrificial oxidation (FIG. **35**). The sacrificial oxide film **62** is formed on the p-well contact region **32** and the source region **30**. The sacrificial oxidation is an example of the oxidation treatment.

(214) The sacrificial oxide film **62** is a silicon oxide film. By forming the sacrificial oxide film **62**, for example, the impurity and damage on the surface of the silicon carbide layer **10** are removed.

(215) Next, the sacrificial oxide film **62** is removed. The sacrificial oxide film **62** is removed using, for example, a wet etching method.

(216) Next, a sidewall **68** is formed on a side of the contact hole **61** (FIG. **36**). The sidewall **68** is formed by deposition and etching of a film by a CVD method. The sidewall **68** is formed of, for example, silicon nitride.

(217) Next, the hydrogen etching treatment for etching the surface of the silicon carbide layer **10** in an atmosphere containing hydrogen gas is performed (FIG. **37**). The temperature of the hydrogen etching treatment is, for example, equal to or higher than 1300° C. and equal to or lower than 1500° C. The surface of the silicon carbide layer **10** is etched by, for example, equal to or greater than 25 nm and equal to or less than 100 nm by performing the hydrogen etching treatment.

(218) The source region **30** covered by the sidewall **68** is not etched, and the p-well contact region

32 exposed from the sidewall **68** is etched.

(219) The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, equal to or greater than 90%. The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, equal to or greater than 95%. The partial pressure of the hydrogen gas in the atmosphere of the hydrogen etching treatment is, for example, 100%. The atmosphere of the hydrogen etching treatment may include, for example, argon gas.

(220) Next, the sidewall **68** is removed (FIG. **38**). The sidewall **68** is removed by, for example, wet etching.

(221) Next, a nickel film **48** is formed on the silicon carbide layer **10** (FIG. **39**). The nickel film **48** is formed on the p-well contact region **32** and the source region **30**. The nickel film **48** is an example of a first metal film. The nickel film **48** is formed using, for example, a sputtering method.

(222) Next, silicidation annealing is performed. A nickel silicide layer **50** is formed by causing the silicon carbide layer **10** to react with the nickel film **48** by silicidation annealing (FIG. **40**). The nickel silicide layer **50** is formed by causing the p-well contact region **32** and source region **30** to react with the nickel film **48**. The nickel silicide layer **50** is an example of the metal silicide layer **13**.

(223) The silicidation annealing is performed, for example, in an atmosphere containing nitrogen. The silicidation annealing is performed, for example, in an atmosphere containing nitrogen gas. The temperature of the silicidation annealing is, for example, equal to or higher than 500° C. and lower than 900° C.

(224) At the time of silicidation annealing, the nickel is diffused from the nickel film **48** into the silicon carbide layer **10**. The nickel is diffused into the source region **30** and the p-well contact region **32**.

(225) Next, an unreacted nickel film **48** is removed (FIG. **41**). The unreacted nickel film is removed by, for example, wet etching.

(226) Thereafter, an aluminum film **51** is formed on the nickel silicide layer **50**. The aluminum film **51** is an example of a second metal film. The second metal film has a chemical composition different from that of the first metal film. The aluminum film **51** is formed by, for example, a sputtering method.

(227) The aluminum film **51** is patterned to finally become the source electrode **12**.

(228) Next, a conductive drain electrode **14** is formed on the silicon carbide layer **10** side opposite to the source electrode **12** (FIG. **42**). In other words, the drain electrode **14** is formed to have the drift region **26** provided between the drain electrode **14** and the source electrode **12**. The drain electrode **14** is formed by, for example, sputtering a nickel film.

(229) The MOSFET **200** illustrated in FIG. **20** is formed by the manufacturing method described above.

(230) Next, a function and an effect of the semiconductor device according to the second embodiment and the method for manufacturing the semiconductor device will be described.

(231) In the MOSFET **200** using silicon carbide, it is desirable to reduce the contact resistance between the n-type source region **30** and the source electrode **12** in order to reduce an on-resistance. In order to realize a stable operation, it is desirable to reduce the contact resistance between the p-type p-well contact region **32** and the source electrode **12**. It is desirable to simultaneously reduce both the contact resistance between the n-type source region **30** and the source electrode **12** and the contact resistance between the p-type p-well contact region **32** and the source electrode **12**.

(232) In the MOSFET **200**, the metal silicide layer **13** is provided between the source region **30** and the source electrode **12** and between the p-well contact region **32** and the source electrode **12**. By using the metal silicide layer **13**, the contact resistance between the source region **30** and the source electrode **12** and the contact resistance between the p-well contact region **32** and the source

electrode **12** are reduced.

(233) As described above, it is known that the contact resistance between an n-type silicon carbide region and the metal silicide layer decreases as the temperature of silicidation annealing increases. On the other hand, it is known that the contact resistance between a p-type silicon carbide region and the metal silicide layer increases as the temperature of silicidation annealing increases.

(234) Therefore, it is difficult to simultaneously reduce both the contact resistance between the n-type source region and the source electrode and the contact resistance between the p-type p-well contact region and the source electrode.

(235) In the method for manufacturing the MOSFET **200** of the second embodiment, when the p-well contact region **32** is formed, carbon is ion-implanted in addition to the ion implantation of aluminum. After the oxidation treatment, the surface of the p-well contact region **32** is etched by the hydrogen etching treatment before the metal silicide layer **13** is formed. By the above-described method, the amount of carbon vacancies in the silicon carbide layer **10** of the p-well contact region **32** is reduced by the same function as that of the contact structure **100** of the first embodiment.

(236) Therefore, the contact resistance between the p-well contact region **32** and the contact electrode **11** decreases. Accordingly, it is possible to simultaneously reduce both the contact resistance between the n-type source region **30** and the source electrode **12** and the contact resistance between the p-type p-well contact region **32** and the source electrode **12**.

(237) From the viewpoint of reducing the contact resistance between the n-type source region **30** and the source electrode **12**, it is preferable not to etch the source region **30** in the hydrogen etching treatment.

(238) From the viewpoint of reducing the contact resistance between the n-type source region **30** and the source electrode **12**, it is preferable to perform a process of increasing the carbon vacancies in the first region in which the source region **30** is formed. Specifically, it is preferable to perform ion implantation of argon into the source region **30**.

(239) By performing the process of increasing the carbon vacancies in the source region **30**, the metal element (M) in the source region **30** easily enters the carbon site in the crystal structure of the silicon carbide. Therefore, for example, even when the temperature of the silicidation annealing is lowered to lower than 900° C., the metal element (M) easily enters the carbon site in the crystal structure of the silicon carbide. Accordingly, the donor concentration of the source electrode **12** increases, and the contact resistance between the n-type source region **30** and the source electrode **12** decreases. The ion implantation of argon (Ar) into the source region **30** can also be performed after activation annealing.

(240) From the viewpoint of increasing the donor concentration of the source region **30**, the temperature of the silicidation annealing is preferably equal to or higher than 500° C., more preferably equal to or higher than 600° C., still more preferably equal to or higher than 700° C., and still more preferably equal to or higher than 800° C.

(241) From the viewpoint of increasing the acceptor concentration of the p-well contact region **32**, the temperature of the silicidation annealing is preferably lower than 900° C.

(242) The intensity of infrared absorption at a wave number of 838 cm^{sup.}-1, which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), corresponds to the density of the carbon vacancies. The infrared absorption at a wave number of 838 cm^{sup.}-1 corresponds to a residual product generated in the silicon carbide layer when the silicon carbide layer is oxidized. The residual product has an Si—O bond. The infrared absorption at wave number 838 cm^{sup.}-1 is based on the presence of the Si—O bond.

(243) When the silicon carbide layer is oxidized, the distortion of the lattice of the silicon carbide is caused to form the carbon vacancies. Therefore, a portion of the silicon carbide layer in which the density of the residual product is high has a high density of carbon vacancies.

(244) In the MOSFET **200** of the second embodiment, a ratio of intensity of infrared absorption at a

wave number of 838 cm.sup.-1 with respect to the intensity of the infrared absorption at a wave number of 970 cm.sup.-1, which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), is a first value in the vicinity of the surface of the p-well contact region **32**. The ratio of intensity of infrared absorption at a wave number of 838 cm.sup.-1 with respect to the intensity of the infrared absorption at a wave number of 970 cm.sup.-1, which is measured by an attenuated total reflection method (ATR method) of a Fourier transform infrared spectroscopy method (FTIR method), is a second value in the vicinity of the surface of the source region **30**. The infrared absorption at a wave number of 970 cm.sup.-1 corresponds to a longitudinal optical phonon mode of the silicon carbide. The intensity of the infrared absorption at a wave number of 970 cm.sup.-1 is used to normalize the intensity of the infrared absorption at a wave number of 838 cm.sup.-1.

(245) The second value is higher than the first value. In other words, the carbon vacancy density in the vicinity of the surface of the source region **30** is higher than the carbon vacancy density in the vicinity of the surface of the p-well contact region **32**. Therefore, in the MOSFET **200**, both the contact resistance between the n-type source region **30** and the source electrode **12** and the contact resistance between the p-type p-well contact region **32** and the source electrode **12** are simultaneously reduced.

(246) Therefore, from the viewpoint of simultaneously reducing both the contact resistance between the n-type source region **30** and the source electrode **12** and the contact resistance between the p-type p-well contact region **32** and the source electrode **12**, the second value is preferably equal to or greater than two times the first value, and more preferably equal to or greater than five times the first value.

(247) In the MOSFET **200** according the second embodiment and the method for manufacturing the MOSFET **200**, both the contact resistance between the source region **30** and the source electrode **12** and the contact resistance between the p-well contact region **32** and the source electrode **12** are simultaneously reduced. Therefore, the operation of the MOSFET **200**, in which the on-resistance is reduced and stable, is realized.

(248) It is also possible to etch the source region **30** and the p-well contact region **32** in the hydrogen etching treatment without forming the sidewall **68** before the etching treatment.

(249) It is also possible to remove the nickel silicide layer after forming the nickel silicide layer and before forming the aluminum film **51**. In this case, the aluminum film **51** is in contact with the source region **30** and the p-well contact region **32**.

(250) As described above, according to the second embodiment, it is possible to realize a semiconductor device capable of reducing the contact resistance between the silicon carbide layer and the metal electrode.

Third Embodiment

(251) An inverter circuit and a driving device according to the third embodiment are an inverter circuit and a driving device, which include the semiconductor device of the second embodiment.

(252) FIG. **43** is a schematic view of the driving device according to the third embodiment. A driving device **700** includes a motor **140** and an inverter circuit **150**.

(253) The inverter circuit **150** includes three semiconductor modules **150a**, **150b**, and **150c** using the MOSFET **200** of the second embodiment as a switching element. By connecting three semiconductor modules **150a**, **150b**, and **150c** in parallel, a three-phase inverter circuit **150** including three AC voltage output terminals U, V, and W is realized. The motor **140** is driven by an AC voltage output from the inverter circuit **150**.

(254) According to the third embodiment, the property of the inverter circuit **150** and the property of the driving device **700** are improved by including the MOSFET **200** with improved property.

Fourth Embodiment

(255) A vehicle according to the fourth embodiment is a vehicle including the semiconductor device according to the second embodiment.

(256) FIG. **44** is a schematic view of the vehicle according to the fourth embodiment. A vehicle **800** of the fourth embodiment is a railway vehicle. The vehicle **800** includes a motor **140** and an inverter circuit **150**.

(257) The inverter circuit **150** includes three semiconductor modules using the MOSFET **200** of the second embodiment as a switching element. By connecting three semiconductor modules in parallel, a three-phase inverter circuit **150** including three AC voltage output terminals U, V, and W is realized. The motor **140** is driven by an AC voltage output from the inverter circuit **150**. Wheels **90** of the vehicle **800** are rotated by the motor **140**.

(258) According to the fourth embodiment, the property of the vehicle **800** is improved by including the MOSFET **200** with improved property.

Fifth Embodiment

(259) A vehicle according to the fifth embodiment is a vehicle including the semiconductor device according to the second embodiment.

(260) FIG. **45** is a schematic view of the vehicle according to the fifth embodiment. A vehicle **900** of the fifth embodiment is an automobile. The vehicle **900** includes a motor **140** and an inverter circuit **150**.

(261) The inverter circuit **150** includes three semiconductor modules using the MOSFET **200** of the first embodiment as a switching element. By connecting three semiconductor modules in parallel, a three-phase inverter circuit **150** including three AC voltage output terminals U, V, and W is realized.

(262) The motor **140** is driven by an AC voltage output from the inverter circuit **150**. Wheels **90** of the vehicle **900** are rotated by the motor **140**.

(263) According to the fifth embodiment, the property of the vehicle **900** is improved by including the MOSFET **200** with improved property.

Sixth Embodiment

(264) An elevator according to the sixth embodiment is an elevator including the semiconductor device according to the second embodiment.

(265) FIG. **46** is a schematic view of an elevator according to the sixth embodiment. An elevator **1000** of the sixth embodiment includes a car **610**, a counterweight **612**, a wire rope **614**, a hoisting machine **616**, a motor **140**, and an inverter circuit **150**.

(266) The inverter circuit **150** includes three semiconductor modules using the MOSFET **200** of the second embodiment as a switching element. By connecting three semiconductor modules in parallel, a three-phase inverter circuit **150** including three AC voltage output terminals U, V, and W is realized.

(267) The motor **140** is driven by an AC voltage output from the inverter circuit **150**. The hoisting machine **616** is rotated by the motor **140**, and the car **610** moves up and down.

(268) According to the sixth embodiment, the property of the elevator **1000** is improved by including the MOSFET **200** with improved property.

(269) As described above, in the first and second embodiments, the case of 4H—SiC has been described as an example of the crystal structure of silicon carbide, but the present disclosure can also be applied to silicon carbide having other crystal structures such as 3C—SiC and 6H—SiC.

(270) The present disclosure can also be applied to the semiconductor device using other silicon carbide, such as a diode and an insulated gate bipolar transistor (IGBT).

(271) The present disclosure can also be applied to a transistor having a trench gate structure in which a gate electrode is provided in a trench instead of a planar gate transistor.

(272) The present disclosure can also be applied to a lateral transistor in which the source electrode and the drain electrode are provided on the same surface of the silicon carbide layer, instead of a vertical transistor.

(273) In the first and second embodiments, the case where the n-type impurity is nitrogen or phosphorus has been described as an example, but arsenic (As) or antimony (Sb) can also be

applied as the n-type impurity.

(274) In the first and second embodiments, the case where the p-type impurity is aluminum has been described as an example, but boron (B), gallium (Ga), and indium (In) can also be applied as the p-type impurity.

(275) In the third to sixth embodiments, the case where the semiconductor device of the present disclosure is applied to a vehicle or an elevator has been described as an example. However, the semiconductor device of the present disclosure can also be applied to, for example, a power conditioner of a solar power generation system.

(276) While certain embodiments have been described, these embodiments have been presented by way of example only, and are not intended to limit the scope of the inventions. Indeed, a method for manufacturing a semiconductor device, a semiconductor device, an inverter circuit, a driving device, a vehicle, and an elevator described herein may be embodied in a variety of other forms; furthermore, various omissions, substitutions and changes in the form of the devices and methods described herein may be made without departing from the spirit of the inventions. The accompanying claims and their equivalents are intended to cover such forms or modifications as would fall within the scope and spirit of the inventions.

Claims

1. A method for manufacturing a semiconductor device, the method comprising: performing first ion implantation of ion-implanting a p-type impurity into a silicon carbide layer in a first projected range and by a first dose amount; performing second ion implantation of ion-implanting carbon (C) into the silicon carbide layer in a second projected range and by a second dose amount; performing a first heat treatment activating the p-type impurity; performing a first oxidation treatment oxidizing the silicon carbide layer; performing an etching treatment etching the silicon carbide layer in an atmosphere containing hydrogen gas; forming a first metal film on the silicon carbide layer, the first metal film containing at least one metal element selected from a group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr); performing a second heat treatment causing the silicon carbide layer to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming a second metal film on the silicon carbide layer, the second metal film having a chemical composition different from a chemical composition of the first metal film.
2. The method for manufacturing a semiconductor device according to claim 1, wherein the silicon carbide layer is etched by equal to or greater than 25 nm when the etching treatment is performed.
3. The method for manufacturing a semiconductor device according to claim 1, further comprising: forming a carbon film on the silicon carbide layer after the performing the first ion implantation and before the performing the first heat treatment, wherein the first oxidation treatment is an ashing treatment removing the carbon film in oxygen plasma.
4. The method for manufacturing a semiconductor device according to claim 1, further comprising: forming an insulating layer on the silicon carbide layer after the performing the first oxidation treatment and before the performing the etching treatment; and forming an opening through which the silicon carbide layer is exposed in the insulating layer, wherein the silicon carbide layer exposed at the opening is etched in the etching treatment.
5. The method for manufacturing a semiconductor device according to claim 4, further comprising a second oxidation treatment of oxidizing the silicon carbide layer exposed at the opening after the forming the opening and before the performing the etching treatment.
6. The method for manufacturing a semiconductor device according to claim 1, wherein the p-type impurity is aluminum (Al).
7. The method for manufacturing a semiconductor device according to claim 1, wherein the second dose amount is greater than the first dose amount.

8. The method for manufacturing a semiconductor device according to claim 1, wherein the first dose amount is equal to or greater than 1×10^{15} cm².
 9. The method for manufacturing a semiconductor device according to claim 1, wherein the second projected range is equal to or greater than 80% and equal to or less than 120% of the first projected range.
 10. The method for manufacturing a semiconductor device according to claim 1, further comprising: removing the metal silicide layer after the forming the metal silicide layer and before the forming the second metal film.
 11. A method for manufacturing a semiconductor device, the method comprising: performing first ion implantation of ion-implanting a p-type impurity into a first region of a silicon carbide layer; performing second ion implantation of ion-implanting carbon (C) into the first region; performing a third ion implantation of ion-implanting an n-type impurity into a second region of the silicon carbide layer; performing a first heat treatment activating the n-type impurity and the p-type impurity; forming a gate insulating layer on the silicon carbide layer; forming a gate electrode on the gate insulating layer; performing an etching treatment etching at least the first region in an atmosphere containing hydrogen gas after the forming the gate electrode; forming a first metal film on the first region and the second region, the first metal film containing at least one metal element selected from a group consisting of nickel (Ni), palladium (Pd), platinum (Pt), and chromium (Cr); performing a second heat treatment causing the first region and second region to react with the first metal film to form a metal silicide layer containing the at least one metal element; and forming a second metal film on the first region and the second region, the second metal film having a chemical composition different from a chemical composition of the first metal film.
 12. The method for manufacturing a semiconductor device according to claim 11, further comprising: performing an oxidation treatment of oxidizing the silicon carbide layer after the performing the first heat treatment and before the performing the etching treatment.
 13. The method for manufacturing a semiconductor device according to claim 11, further comprising: forming an insulating layer on the silicon carbide layer after the forming the gate electrode and before the performing the etching treatment; and forming an opening through which at least the first region is exposed in the insulating layer, wherein the first region exposed at the opening is etched in the etching treatment.
 14. The method for manufacturing a semiconductor device according to claim 11, wherein the first region and the second region are etched in the etching treatment.
 15. The method for manufacturing a semiconductor device according to claim 11, wherein the first region is etched by equal to or greater than 25 nm when the etching treatment is performed.
 16. The method for manufacturing a semiconductor device according to claim 11, further comprising: performing an ion implantation of ion-implanting argon into the second region before the performing the first heat treatment.
 17. The method for manufacturing a semiconductor device according to claim 11, wherein a temperature of the second heat treatment is less than 900° C.
-