

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12409588
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Suzuki; Takahiro et al.

Product and method of manufacturing product

Abstract

A product includes a first area and a second area. Each area includes areas having a first optical property and areas having a second optical property. The areas having the first optical property and the areas having the second optical property are arranged under a specific rule. In the first area, convex portions whose height is equal to or smaller than a predetermined height or no convex portions are formed. In the second area, convex portions whose height is larger than the predetermined height are formed.

Inventors: Suzuki; Takahiro (Tokyo, JP), Oikawa; Kei (Kawasaki, JP), Arai; Kimitaka (Yokohama, JP)

Applicant: CANON KABUSHIKI KAISHA (Tokyo, JP)

Family ID: 69797218

Assignee: Canon Kabushiki Kaisha (Tokyo, JP)

Appl. No.: 17/005723

Filed: August 28, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20200391419 A1	Dec. 17, 2020

Foreign Application Priority Data

JP	2018-039006	Mar. 05, 2018
JP	2018-108091	Jun. 05, 2018
JP	2018-166090	Sep. 05, 2018
JP	2019-027995	Feb. 20, 2019

Related U.S. Application Data

continuation parent-doc WO PCT/JP2019/007830 20190228 PENDING child-doc US 17005723

Publication Classification

Int. Cl.: B29C45/00 (20060101)

U.S. Cl.:

CPC B29C45/0017 (20130101); B29C45/0001 (20130101); B29K2995/0022 (20130101)

Field of Classification Search

CPC: B29C (45/0017); B29C (45/0001); B29K (2995/0022)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8440287	12/2012	Shimizu et al.	N/A	N/A
8507073	12/2012	Nishikawa et al.	N/A	N/A
10798838	12/2019	Oikawa	N/A	N/A
2004/0265543	12/2003	Komatsu et al.	N/A	N/A
2006/0134381	12/2005	Homburg	428/141	B60R 13/0256
2011/0033670	12/2010	Nishikawa	428/162	B29C 45/16
2012/0196086	12/2011	Shimizu	428/141	B60R 13/0256
2018/0063979	12/2017	Oikawa	N/A	N/A
2019/0084200	12/2018	Oikawa	N/A	N/A
2019/0389110	12/2018	Sano et al.	N/A	N/A
2020/0031023	12/2019	Nagoya et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1539617	12/2003	CN	N/A
1539617	12/2003	CN	N/A
101688934	12/2009	CN	G02B 5/1871
101945745	12/2010	CN	N/A
101945745	12/2010	CN	N/A
2581248	12/2012	EP	B60K 1/00
59-123628	12/1983	JP	N/A
8-72141	12/1995	JP	N/A
2006-175863	12/2005	JP	N/A
2006-175863	12/2005	JP	N/A
2009-517246	12/2008	JP	N/A

2009-517246	12/2008	JP	N/A
2009134271	12/2008	JP	N/A
2015-020367	12/2014	JP	N/A
2015-74400	12/2014	JP	N/A
2018-176564	12/2017	JP	N/A
2007/061201	12/2006	WO	N/A
2011/043117	12/2010	WO	N/A
2019/172075	12/2018	WO	N/A

OTHER PUBLICATIONS

JP 2009134271 A Machine Translation (Year: 2009). cited by examiner

International Search Report in International Application No. PCT/JP2019/007830 (May 2019).
cited by applicant

Third Office Action in Chinese Application No. 201980016816.4 (Sep. 2022). cited by applicant

First Office Action in Chinese Application No. 201980016816.4 (Sep. 2021). cited by applicant

Primary Examiner: Figg; Travis M

Attorney, Agent or Firm: Venable LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a Continuation of International Patent Application No. PCT/JP2019/007830, filed Feb. 28, 2019, which claims the benefit of Japanese Patent Application No. 2018-039006, filed Mar. 5, 2018, Japanese Patent Application No. 2018-108091, filed Jun. 5, 2018, Japanese Patent Application No. 2018-166090, filed Sep. 5, 2018, and Japanese Patent Application No. 2019-027995, filed Feb. 20, 2019, those of which are hereby incorporated by reference herein in their entirety.

BACKGROUND OF THE INVENTION

Field of the Invention

(1) The present invention relates to a resin component whose outer surface includes an area in which a process such as lettering is performed, the resin component on which the process such as lettering has been performed, an electronic device in which the resin component is used, and a method of manufacturing the resin component.

Description of the Related Art

(2) A plate-like or box-like resin component is used in a housing or a case of an electronic device, such as a printer. The outer surface of the resin component is required to have attractive design and functionality such as soil resistance and scratch resistance. For example, in a conventional art, Japanese Patent Application Publication No. 2009-134271 proposes a configuration that achieves both aesthetic appearance and inconspicuousness of dirt such as fingerprints. In this configuration, a design pattern is formed on an external surface, and includes a flat glossy surface and a nonglossy surface having convex portions that project from a flat surface.

(3) On the outer surface of the resin component, which constitutes a housing or a case of an electronic device, a maker-name or model-name logo, or a design or a trade mark including numerals, characters, or a figure may be formed. Generally, such information is given, after the resin component is molded, by coating or surface treatment performed by heating. Such coating is performed by using a method such as hot stamping, which thermally transfers foil onto the resin component. The foil is made from metal and pigment for example, and serves as an information

bearing member. In another case, the coating may be performed by sticking an information bearing member such as a seal, or by painting or spraying paint, pigment, or powder.

(4) In a case where a resin component having the above-described convex portions, or a concave-and-convex structure, is manufactured through injection molding or the like, the outer surface of the resin component may include a plurality of surfaces having different angles with respect to a mold releasing direction. In this case, the concave-and-convex structure formed on the surfaces may have various limitations. For example, if a component surface is curved or inclined with respect to the mold releasing direction, it is necessary to prevent the concave-and-convex structure of the component surface from becoming a so-called undercut, for achieving good releasability of the mold. For this reason, there is a case in which no concave-and-convex structure is formed in one area of the outer surface of the resin component. In addition, there is a case in which separate molds are used for portions whose concave-and-convex structures have different orientations. In this case, each mold will be opened, for example, toward a direction in which a corresponding concave-and-convex structure is prevented from becoming an undercut.

(5) Note that the external surface or the outer surface designed as described above, or the external surface or the outer surface on which the coating process or the surface treatment process is performed is not necessarily limited to a housing of an electronic device, or a front surface of a case of the electronic device. For example, a door, a hatch, or a cover of a device may include a resin component that is usually not exposed but can be seen by a user when the door, the hatch, or the cover is opened; and the above-described design may be formed on such a resin component. Hereinafter, a surface (component surface) of the resin component, which has a design that can be visually recognized by a user, is simply referred to as an outer surface.

(6) In a case where a logo or the like is given to an outer surface of a resin component through a process such as hot stamping, the outer surface is required to be smooth to some extent. That is, the outer surface is required to be a surface that can be stably processed. However, the outer surface of the resin component may have a design pattern having a difference in height (concave and convex portions) for the design and functionality, as described above. However, if the process such as hot stamping is performed on the design pattern having the difference in height, the logo or the like may not be accurately transferred onto the resin component, or may not be fixed to the resin component and may easily peel off the resin component. As a result, the quality of the logo or the like may deteriorate. To avoid this problem, one solution is to smooth an area (hereinafter referred to as a first area) of the outer surface, on which the logo is to be formed, by forming no design patterns on the area. However, since the presence and absence of the design pattern is easily recognized by visual characteristics of humans, a boundary between the first area and the other area (hereinafter referred to as a second area) becomes conspicuous, possibly deteriorating the design.

(7) In addition, if no concave-and-convex structure is formed on a curved surface for improving the mold releasability, a conspicuous gap that is visually recognized by humans is formed on the outer surface of the resin component in the vicinity of a boundary between an area in which the concave-and-convex structure is formed and an area in which no concave-and-convex structure is formed, possibly deteriorating the design.

(8) In addition, if separate molds are used for avoiding an undercut, an undesired artifact, such as a parting line, may be produced at a position corresponding to a place where molds are fixed to each other. Since such a parting line is produced in a portion of the resin component in which the concave-and-convex structure is continuously formed, it is difficult to remove only the parting line without damaging the concave-and-convex structure, in a postprocess such as cutting or grinding.

(9) For this reason, it has been desired to achieve a technique that forms a logo or the like, through a process, on an outer surface on which a design pattern having a difference in height (concave and convex portions) is formed, and that allows an inclined surface or a curved surface to be formed in the outer surface, without significantly deteriorating the quality of external appearance in design.

SUMMARY OF THE INVENTION

(10) According to a first aspect of the present invention, a product includes a first area and a second area, each area including areas having a first optical property and areas having a second optical property, the areas having the first optical property and the areas having the second optical property are arranged under a specific rule. In the first area, convex portions whose height is equal to or smaller than a predetermined height or no convex portions are formed. In the second area, convex portions whose height is larger than the predetermined height are formed.

(11) According to a second aspect of the present invention, a method of manufacturing a product includes molding a molded product including an outer surface, and processing a first area of the molded product. The outer surface includes the first area and a second area in which areas having a first optical property and areas having a second optical property are arranged under a specific rule. Convex portions whose height is equal to or smaller than a predetermined height or no convex portions are formed in the first area. Convex portions whose height is larger than the predetermined height are formed in the second area.

(12) Further features of the present invention will become apparent from the following description of exemplary embodiments with reference to the attached drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIG. 1 is a perspective view illustrating an external appearance of a printer that is an electronic device of a first embodiment of the present invention.
- (2) FIG. 2A is a schematic plan view illustrating a structure of a resin component of a conventional art.
- (3) FIG. 2B is a schematic cross-sectional view illustrating the structure of the resin component of the conventional art.
- (4) FIG. 3A is a schematic plan view illustrating a structure of a resin component of the first embodiment of the present invention.
- (5) FIG. 3B is a schematic cross-sectional view illustrating the structure of the resin component of the first embodiment of the present invention.
- (6) FIG. 4A is one example of a surface pattern that can be applied for the electronic device of the first embodiment of the present invention.
- (7) FIG. 4B is one example of a surface pattern that can be applied for the electronic device of the first embodiment of the present invention.
- (8) FIG. 4C is one example of a surface pattern that can be applied for the electronic device of the first embodiment of the present invention.
- (9) FIG. 5 is a schematic diagram illustrating one example of a manufacturing apparatus that machines a mold used for the resin component of the first embodiment of the present invention.
- (10) FIG. 6A is a diagram illustrating a machining process for the mold used for the resin component of the first embodiment of the present invention.
- (11) FIG. 6B is a diagram illustrating a machining process for the mold used for the resin component of the first embodiment of the present invention.
- (12) FIG. 7A is a diagram illustrating a machining process for the mold used for the resin component of the first embodiment of the present invention.
- (13) FIG. 7B is a diagram illustrating a machining process for the mold used for the resin component of the first embodiment of the present invention.
- (14) FIG. 8A is a diagram illustrating a structure of a surface of a resin component of Example 1.
- (15) FIG. 8B is a diagram illustrating an optical property of the surface of the resin component of Example 1.
- (16) FIG. 8C is a diagram illustrating a structure of a section of the resin component of Example 1.

- (17) FIG. 9A is a diagram illustrating a structure of a surface of a resin component of Example 2.
- (18) FIG. 9B is a diagram illustrating an optical property of the surface of the resin component of Example 2.
- (19) FIG. 9C is a diagram illustrating a structure of a section of the resin component of Example 2.
- (20) FIG. 10A is a plan view of the whole of a resin component of Example 2.
- (21) FIG. 10B is a diagram illustrating a structure of a surface of the resin component of Example 2.
- (22) FIG. 10C is a diagram illustrating a structure of a section of the resin component of Example 2.
- (23) FIG. 10D is a diagram illustrating an optical property of the surface of the resin component of Example 2.
- (24) FIG. 11A is a plan view of the whole of a resin component of Example 3.
- (25) FIG. 11B is a diagram illustrating a structure of a surface of the resin component of Example 3.
- (26) FIG. 11C is a diagram illustrating a structure of a section of the resin component of Example 3.
- (27) FIG. 11D is a diagram illustrating an optical property of the surface of the resin component of Example 3.
- (28) FIG. 12A is a diagram illustrating a machining process for a mold used in Example 3.
- (29) FIG. 12B is a diagram illustrating a relationship between the depth of cut of the mold and the glossiness intensity of a resin component.
- (30) FIG. 13 is a block diagram of a control system of a manufacturing apparatus used for the mold.
- (31) FIG. 14 is a block diagram of the control system of the manufacturing apparatus used for the mold.
- (32) FIG. 15 is a flowchart illustrating procedures for controlling the manufacturing apparatus used for the mold.
- (33) FIG. 16 is a diagram illustrating one example of a glossiness map.
- (34) FIG. 17 is a table illustrating one example of cutting tool information.
- (35) FIG. 18 is a flowchart illustrating other procedures for controlling the manufacturing apparatus used for the mold.
- (36) FIG. 19A is a diagram illustrating an optical property of a surface of an electronic device of Example 3.
- (37) FIG. 19B is a diagram illustrating a structure of a section of the electronic device of Example 3.
- (38) FIG. 20A is a diagram illustrating a structure of a surface of a resin component which is the first embodiment of the present invention, and on which a process to give a logo or the like has been performed.
- (39) FIG. 20B is a diagram illustrating a structure of a section of the resin component which is the first embodiment of the present invention, and on which the process to give a logo or the like has been performed.
- (40) FIG. 21A is a diagram illustrating a structure of a surface of the resin component which is the first embodiment of the present invention, and on which a process to give a logo or the like has been performed.
- (41) FIG. 21B is a diagram illustrating a structure of a section of the resin component which is the first embodiment of the present invention, and on which the process to give a logo or the like has been performed.
- (42) FIG. 22A is a diagram illustrating a structure of an outer surface of a conventional resin component.
- (43) FIG. 22B is a diagram illustrating a structure of a section of the conventional resin component.

- (44) FIG. 23A is a diagram illustrating an example structure of an outer surface of a resin component that is a second embodiment of the present invention.
- (45) FIG. 23B is a diagram illustrating an example structure of a section of the resin component that is the second embodiment of the present invention.
- (46) FIG. 24A is a diagram illustrating a machining process for a mold used in the second embodiment.
- (47) FIG. 24B is a diagram illustrating a machining process for the mold used in the second embodiment.
- (48) FIG. 24C is a diagram illustrating a machining process for the mold used in the second embodiment.
- (49) FIG. 25A is a diagram illustrating a structure of a surface of a resin component of Example 4.
- (50) FIG. 25B is a diagram illustrating an optical property of the surface of the resin component of Example 4.
- (51) FIG. 25C is a diagram illustrating a structure of a section of the resin component of Example 4.
- (52) FIG. 26A is a diagram illustrating a structure of a surface of a resin component of Example 5.
- (53) FIG. 26B is a diagram illustrating an optical property of the surface of the resin component of Example 5.
- (54) FIG. 26C is a diagram illustrating a structure of a section of the resin component of Example 5.

DESCRIPTION OF THE EMBODIMENTS

(55) Hereinafter, embodiments of the present invention will be described with reference to the accompanying drawings. Note that since the configurations described below are merely examples, detailed configurations or the like may be changed as appropriate by a person skilled in the art, without departing the spirit of the present invention.

(56) The product in the following embodiments can be used for an electronic product, such as a recording apparatus (printer), that includes electronic components, and for other products, such as an exterior component or an interior component of a vehicle such as an automobile, that are required to have high quality external appearance. In the following embodiments, the resin component is used, for example, as an exterior component of a printer (recording apparatus) with a document reader.

First Embodiment

(57) FIG. 1 is an external view of an electronic device that is one example of a product for which the present invention has been applied. In particular, the electronic device is a printer. In FIG. 1, a printer 1 is a multifunction printer, for example; and outer surfaces (exterior surfaces) of a document cover 12 and a housing 10 are made of resin with a predetermined color, such as black. Since an outer surface 11 of the printer 1 is conspicuous to a user, the outer surface 11 is required to have high quality external appearance, and thus has a design pattern.

(58) FIGS. 2A and 2B illustrate a structure of an outer surface of a conventional product. FIG. 2A illustrates the whole of the outer surface 11, and FIG. 2B illustrates a cross section of the product, taken along an alternate long and short dashed line of FIG. 2A. As illustrated in FIG. 2A, the conventional outer surface 11 includes a first area 30 and a second area 31. The first area 30 is an area in which a piece of information, such as a logo, can be formed by printing or the like. The second area 31 is an area other than the first area.

(59) As illustrated in FIG. 2B, the second area 31 of FIG. 2A has a surface pattern including convex portions 41 (e.g. deep-color portions in FIG. 2A) and flat portions 42 (e.g. white-color portions in FIG. 2A). The convex portions 41 and the flat portions 42 have different optical properties. Thus, the second area 31 of the outer surface 11 has the design pattern constituted by the convex portions and the flat portions, for the design and functionality. In contrast, the first area 30 has no convex portions of the design pattern, as illustrated in FIG. 2B, for satisfactorily performing a process such

as hot stamping for giving a logo or the like. In such a conventional structure, since the design pattern is discontinuous, a boundary between the first area **30** and the second area **31** is conspicuous, disadvantageously deteriorating the design.

(60) In the first embodiment, however, for suppressing the deterioration of quality of external appearance caused by the conspicuous boundary between the first area **30** and the second area **31**, a surface pattern as illustrated in FIGS. **3A** and **3B** is formed on the outer surface **11** of the resin component, which constitute the housing of the electronic device. Like FIGS. **2A** and **2B**, FIG. **3A** illustrates the whole of the outer surface **11**, and FIG. **3B** illustrates a cross section, taken along an alternate long and short dashed line of FIG. **3A**.

(61) In the first embodiment, the design pattern (surface pattern) is formed across the first area **30** and the second area **31** on the outer surface **11** of the resin component of the housing of the electronic device. The design pattern (surface pattern) is constituted by areas with different optical properties (in particular, glossiness values). The areas constituting the surface pattern and having different glossiness values are constituted by nonglossy portions **51** and glossy portions **52**, as illustrated in FIG. **3B**. The nonglossy portions **51** have a first optical property and a lower glossiness value, and the glossy portions **52** have a second optical property and a higher glossiness value.

(62) In the second area **31** illustrated in FIGS. **3A** and **3B**, each of the nonglossy portions **51** corresponds to a fine concave-and-convex structure formed on a top surface of a corresponding convex portion **41** whose height is larger than a predetermined height, and each of the glossy portions **52** corresponds to the surface of a corresponding flat portion **42**. The second area **31** is formed so as to give an observer the same visual impression as that to the surface pattern of the second area of FIGS. **2A** and **2B**. In the first area **30**, the convex portions **41** are not formed, and each of the nonglossy portions **51** is formed as a fine concave-and-convex structure formed on a flat surface. In another case, in the first area **30**, the convex portions whose height is smaller than the above-described predetermined height is formed, and each of the nonglossy portions **51** is formed as a fine concave-and-convex structure formed on a top surface of a corresponding convex portion. Thus, a fine concave-and-convex structure corresponds to a nonglossy portion **51**, and the surface of a flat portion corresponds to a glossy portion **52**.

(63) In the present embodiment, the nonglossy portion **51** having the first optical property and a lower glossiness value has the fine concave-and-convex structure, and the glossy portion **52** having the second optical property and a higher glossiness value has the flat surface. Thus, the nonglossy portion **51** and the glossy portion **52** have different surface roughness values.

(64) In the present embodiment, a specific rule for arranging areas having the first optical property and areas having the second optical property is equal to a specific rule for arranging the convex portions whose height is equal to or smaller than the predetermined height and the convex portions whose height is larger than the predetermined height. However, since the nonglossy portion and the glossy portion can be formed by changing surface roughness, the specific rule for arranging areas having different optical properties may be different from the specific rule for arranging the convex portions whose height is equal to or smaller than the predetermined height and the convex portions whose height is larger than the predetermined height. That is, the arrangement pattern of the convex portions may be different from the design pattern in which the areas having different optical properties are arranged. That is, the arrangement pattern of the convex portions may be different from the pattern determined under a specific rule which arranges the areas having the first optical property and the areas having the second optical property.

(65) As described above, on the top surface of the nonglossy portion **51**, the fine concave-and-convex structure is formed for scattering incident light. The fine concave-and-convex structure is so fine that the structure is impossible or difficult to visually recognize through the naked eye. In contrast, the surface of the glossy portion **52** is formed smooth for specularly reflecting incident light.

(66) That is, in the first embodiment, the nonglossy portion **51** and the glossy portion **52** have different surface roughness values. Specifically, as illustrated in FIG. 3B, the convex portion **41** has the fine concave-and-convex structure formed on the top surface (surface) of the convex portion **41**, and the surface of the flat portion **42** is formed smooth.

(67) In addition, in the first embodiment, the design pattern (surface pattern) constituted by the nonglossy portion **51** and the glossy portion **52** is formed also in the first area **30**. However, the high convex portion **41** as in the second area may not be formed in the first area **30**.

(68) Thus, the height of the convex portion of the first area **30**, that is, the height from the flat surface to the top surface of the convex portion is significantly smaller than the height of the convex portion of the second area **31**.

(69) For example, in the second area **31**, it is preferable that the convex portion **41** project from the flat portion **42** by a value equal to or larger than $40\text{ }\mu\text{m}$ and equal to or smaller than $500\text{ }\mu\text{m}$. If the height of the convex portion **41** is equal to or larger than $40\text{ }\mu\text{m}$, the convex portion **41** can have soil resistance, so that fingerprints hardly adhere to the molded product. However, if the height of the convex portion **41** is equal to or larger than $500\text{ }\mu\text{m}$, the area of the glossy portion that can be visually recognized becomes smaller depending on angles, so that a sense of high quality in design is suppressed.

(70) The difference in height between the flat portion **42** and the convex portion **41** of the second area **31**, that is, the difference in height between the glossy portion **52** and the nonglossy portion **51** can be obtained, for example, by using a white-light interferometer and measuring a height of the nonglossy portion with respect to the glossy portion. For example, the difference in height is defined as an average of values obtained by performing measurement at ten points of a portion of the molded product. The size of the portion is $1.0\times 1.4\text{ mm}$, and the measurement is performed by using 3D optical profiler NewView7000 made by ZYGO Corporation and an objective lens with a magnification of 10 times.

(71) The difference in glossiness, which is the difference in optical property between the nonglossy portion **51** and the glossy portion **52**, may have any value as long as the difference in glossiness can be visually perceived by a user. Preferably, the difference in glossiness is ten or more. Note that glossiness values in this description were measured by using a glossmeter, which is designed to measure a specular glossiness at a reflection angle of 60° under JIS Z 8741. The measurement values on glossiness can be obtained by using a handy type gloss meter PG-1 made by NIPPON DENSHOKU INDUSTRIES CO. LTD. Specifically, the measurement values on glossiness can be obtained by setting the reflection angle at 60° , and pressing a measurement switch in a state where a photometer of the glossmeter is pressed against a glossy portion of the molded product.

(72) In the first area **30**, the difference in height between convex portions of the fine concave-and-convex structure, which forms the nonglossy portion **51**, and the flat portion **42**, which forms the glossy portion **52**, is the difference in height between the nonglossy portion **51** and the glossy portion **52**. The fine concave-and-convex structure of the nonglossy portion **51** is formed such that the difference in height is equal to or smaller than $15\text{ }\mu\text{m}$. If the fine concave-and-convex structure is formed such that the difference in height is equal to or smaller than $15\text{ }\mu\text{m}$, the nonglossy portion is formed such that each of the concave and convex portions is inconspicuous, and the process such as hot stamping is possible. The present inventors have found through an experiment that if the maximum step is equal to or smaller than $15\text{ }\mu\text{m}$, the performance of transfer or fixing in hot stamping or painting is not lowered, and a design or a trade mark, such as a logo, numerals, characters, or a figure, can be given through the process.

(73) FIGS. 20A and 21A are plan views in which a character “A” is given to the first area **30** as one example of information **301**, such as characters, numerals, a figure, or a logo. FIGS. 20B and 21B respectively illustrate cross sections taken along an alternate long and short dashed line of FIGS. 20A and 21A. If a portion to which the information has been given has a third optical property different from the first optical property and the second optical property, it is preferable because the

information can be visually recognized easily.

(74) As illustrated in FIG. 20B, when a sheet of foil is disposed on the fine concave-and-convex structure through hot stamping, or when ink is applied to the fine concave-and-convex structure through printing, the portion to which the information **301** has been given may have a height slightly larger than the height of the convex portions of the fine concave-and-convex structure.

(75) In contrast, depending on stamping conditions applied when the information **301**, such as characters, numerals, a figure, or a logo, is given, the portion to which the information **301** has been given may have a height slightly smaller than the height of the convex portions of the fine concave-and-convex structure, as illustrated in FIG. 21B.

(76) In either case, in the first embodiment, the information **301**, such as characters, numerals, a figure, or a logo, can be stably given to the first area **30** through the process.

(77) As described above, in the first area **30** of the first embodiment, although the convex portions **41** as high as the convex portions **41** of the second area **31** are not formed, a surface pattern of nonglossy portions is formed by the fine concave-and-convex structure whose height is equal to or smaller than 15 μm , which allows the process to be performed on the first area **30**. In addition, the design pattern including the glossy portion and the nonglossy portion is continuously formed on both the first area **30** and the second area **31**, across the boundary between the first area **30** and the second area **31**. Thus, the continuity of the design pattern is kept across the boundary between the first area **30** and the second area **31**, so that the boundary is advantageously inconspicuous (that is, difficult to visually recognize). In the first area **30**, the information **301**, such as a logo, numerals, characters, or a figure, that represents a design or a trade mark is given through a process such as hot stamping. Thus, in the first embodiment, since a user perceives as the design pattern continuously extends from the second area **31** to a portion of the first area **30** that is very close to the information, such as a logo, numerals, characters, or a figure, that represents a design or a trade mark, the aesthetic appearance will not be lost. Thus, in the first embodiment, the design pattern (surface pattern) formed by arranging the areas with different optical properties and the information, such as a logo, that has been given through the process can coexist, with good appearance, on the outer surface of the resin component.

(78) The surface pattern of glossy and nonglossy portions can be achieved as a geometrical design pattern, such as a checked pattern (see later-described FIGS. 8B and 9B, for example), that is formed on the outer surface **11** of the resin component. In this case, it is preferable that an area in which a convex portion (nonglossy portion) is formed and an area in which a flat portion (glossy portion) is formed have a width of 1 mm or more in a plan view. If the width is less than 1 mm, the glossy portion will be difficult for a user to visually recognize and may not be perceived as an intended pattern.

(79) Note that the geometrical structure of the surface pattern given to the outer surface **11** of the resin component and constituted by the areas of glossy and nonglossy (or concave and convex) portions is not limited to the checked pattern. That is, the geometrical structure of the surface pattern may be any pattern as long as the concave and convex portions and the glossiness allow an observer to visually recognize the surface pattern and find the aesthetic appearance.

(80) FIGS. 4A to 4C illustrate examples of a geometrical structure of the regular surface pattern formed on the outer surface **11** of the resin component and constituted by the areas of glossy and nonglossy portions (or the areas having different surface roughness values). FIG. 4A illustrates a polka-dotted pattern **111** in which circles are arranged. FIG. 4B illustrates a star-shaped pattern **112** in which stars are arranged. FIG. 4C illustrates a scale pattern **113** in which triangles are arranged. Thus, if the surface pattern, in which an identically-shaped glossy portion and an identically-shaped nonglossy portion (or portions having different surface roughness values) are repeatedly disposed under a specific rule, is used, the resin component can be easily manufactured advantageously. The patterns illustrated in FIGS. 4A to 4C are merely examples. Thus, the structure of the surface pattern in which the areas having different glossiness values (or the areas having different surface

roughness values) are alternately arranged is not limited to these examples.

(81) In the first embodiment, the material of the component including the outer surface **11** that constitutes a housing or a case of an electronic device may be a resin material such as ABS or HIPS (high impact polystyrene).

(82) Next, a method of manufacturing a resin component of the first embodiment will be described. The resin component of the first embodiment, on which the above-described design pattern (surface pattern) is formed in the second area **31** and the first area **30**, can be produced by using a so-called injection molding method, which injects resin from a gate into a cavity formed in a mold, and fills the cavity with the resin (molding process). Then, the information such as a logo is given to the first area **30** through a process such as hot stamping (machining process).

(83) With these processes, the resin component that can be used as a housing of an electronic device such as a printer is completed.

(84) FIG. 5 illustrates a configuration of a machining center that manufactures a mold used to mold the resin component of the first embodiment. A machining center **90** of FIG. 5 includes a machine body **91** and a control device **92**. The cavity may be formed by a plurality of pieces (cavity pieces) each of which forms one portion of the mold. Thus, if the cavity is formed by the cavity pieces, a transfer surface can be divided into pieces of the surface, and the pieces of the surface can be individually machined. Thus, even though a molded product has a complex shape, production cost for the mold can be reduced.

(85) The machine body **91** is used to manufacture the mold (cavity piece) **93** by cutting the mold **93**, which is an object to be machined. The machine body **91** includes a spindle **95**, an X stage **96**, a Y stage **97**, and a Z stage **98**. The spindle **95** is a spindle that supports a cutting tool **94**.

(86) As the cutting tool **94**, an end mill can be suitably used. The spindle **95** rotates the cutting tool **94** on a Z axis. The Z stage **98** supports the spindle **95**, and moves the cutting tool **94** in a Z-direction with respect to the mold **93**. Similarly, the X stage **96** moves the cutting tool **94** in an X-direction with respect to the mold **93**, and the Y stage **97** moves the cutting tool **94** in a Y-direction with respect to the mold **93**. With such a configuration, the machine body **91** moves an end of the cutting tool **94** in the X-, Y-, and Z-direction with respect to the mold **93**, while rotating the cutting tool **94**.

(87) The control device **92** is a computer including a CPU and a memory, and controls the machine body **91** depending on NC data **99**. The NC data **99** contains various instructions used in the cutting process, such as the amount of movement in the X-direction, the amount of movement in the Y-direction, the amount of movement in the Z-direction, rotational speed of the spindle, feed speed in the X-direction, feed speed in the Y-direction, and feed speed in the Z-direction. The control device **92** controls the machine body **91**, and thereby can move the cutting tool **94** with respect to the mold **93** while rotating the cutting tool **94**, so that a three-dimensional shape based on the NC data **99** can be formed in the mold **93** by cutting the mold **93**.

(88) FIGS. 6A, 6B, 7A, and 7B illustrate processes for manufacturing the mold **93** used to mold the resin component of the first embodiment. FIG. 6A illustrates a first mold-machining process, FIG. 6B illustrates a second mold-machining process, and FIGS. 7A and 7B illustrate a third mold-machining process.

(89) First, in the first mold-machining process illustrated in FIG. 6A, a surface **101** of the mold **93** is roughly machined. A radius end mill **102** is attached to the machining center of FIG. 5, as a cutting tool; and the surface of the mold **93** is cut, depending on the NC data **99**, by scanning the surface **101** while rotating the radius end mill **102**. Preferably, the surface **101** is cut in the first mold-machining process such that the flatness of the surface **101** is 10 μm or less, for eliminating a smoothing process to be performed in the second mold-machining process.

(90) In the second mold-machining process of FIG. 6B, the surface **101** of the mold **93** is ground into a mirror surface by using a rotary grinder **103** and diamond paste. When the smooth mirror surface is transferred to the resin, the transferred portion forms the above-described glossy portion.

Preferably, the surface **101** is ground in the second mold-machining process such that the flatness of the surface **101** is 5 μm or less, so that no difference in depth is produced in concave portions **104** when the concave portions **104** are machined in the third mold-machining process.

(91) In the third mold-machining process, the surface **101** of the mold **93** is machined by using a ball end mill **106**. FIG. 7A illustrates a process for forming a portion of the mold used to transfer the shape of the above-described second area **31** to the resin component. FIG. 7B illustrates a process for forming a portion of the mold used to transfer the shape of the first area **30** to the resin component.

(92) As illustrated in FIG. 7A, when the portion of the mold corresponding to the second area **31** is machined, the portion is cut and scanned, depending on the NC data **99**, while the ball end mill **106** is rotated, so that the concave portions **104** are formed. When the concave portions **104** are transferred to the resin component, the convex portions **41** are formed in the resin component. The portion of the mold is further scanned by the ball end mill **106** for forming a plurality of fine concave portions **105** in the bottom surface of each concave portion **104**. With this operation, a fine concave-and-convex structure to form the rough surface that is a nonglossy portion is formed in the bottom surface of the concave portion **104**.

(93) When the fine concave-and-convex structure is transferred to the resin component through injection molding, a fine concave-and-convex structure (rough surface) is formed on the convex portion **41**. The fine concave-and-convex structure formed on the convex portion **41** is a light scattering surface of the nonglossy portion **51**. In addition, as illustrated in FIG. 7B, for forming a portion of the mold corresponding to the first area **30**, a plurality of concave portions **105** are formed in the portion of the surface **101** of the mold at positions corresponding to the nonglossy portions **51**. As illustrated in FIG. 7B, in the first area **30**, the concave portions as large as the concave portions **104** of FIG. 7A are not formed. As illustrated in FIGS. 7A and 7B, the portions of the mold in which many fine concave portions **105** are formed correspond to the nonglossy portions **51** that scatter light, and the flat portions of the mold in which the fine concave portions **105** are not formed correspond to the glossy portions **52**.

(94) Note that the material of the mold **93** machined as described above may be stainless steel. However, the material may be any other material for the machinability and durability in the injection molding.

(95) In the above description, the molding for the resin component through injection molding and the manufacturing process for the mold have been described. However, the manufacturing method is not limited to the above description. The molding for the above-described resin component including the second area **31** and the first area **30** may be performed using another appropriate method other than the above-described injection molding.

(96) Hereinafter, specific examples in the first embodiment will be described.

Example 1

(97) FIGS. 8A to 8C are diagrams for illustrating a resin component **80** of Example 1. FIG. 8A illustrates a height distribution of an outer surface of the resin component **80**, FIG. 8B illustrates a glossiness distribution of the outer surface of the resin component **80**, and FIG. 8C illustrates a shape of a cross section in the vicinity of the outer surface of the resin component **80**.

(98) In Example 1, as illustrated in FIG. 8B, a checked design pattern in which glossy portions **85** and nonglossy portions **84** are arranged was formed on the resin component **80**. The thickness of the resin component **80** was set at 1.6 mm, as an example. As illustrated in FIG. 8B, the pitch of the checked pattern was set at 7 mm, and the checked pattern was formed continuously in a first area **81** and a second area **87**. As illustrated in FIG. 8C, in the second area **87**, the difference in height between a convex portion **82** (nonglossy portion **84**) and a flat portion **83** (glossy portion **85**), which are adjacent to each other, was set at 50 μm . The difference in height can produce an optically large contrast, but is not suitable for the process to give a logo or the like. In the first area **81** which is formed in a center portion, and to which the process to give a logo or the like is

performed in a postprocess, the difference in height between the nonglossy portion **84** and the glossy portion **85**, that is, the height of the fine concave-and-convex structure of the nonglossy portion **84** with respect to the flat surface of the glossy portion **85** was set at 5 to 15 μm . The difference in height was determined so as not to affect the process to give the logo to the first area **81**.

(99) As illustrated in FIG. **8B**, the checked design pattern is a glossiness pattern in which the nonglossy portions **84** (with a glossiness value of 30) and the glossy portions **85** (with a glossiness value of 80) are arranged. In FIG. **8C**, in the second area **87**, the convex portions **82** correspond to the nonglossy portions **84**, and the flat portions **83** correspond to the glossy portions **85**. On the top surface of each convex portion **82**, which is a nonglossy portion **84**, a fine concave-and-convex structure having a height of 5 μm was formed so that the glossiness value was set at 30. The glossy portion **85** was formed as a flat surface on which the fine concave-and-convex structure was not formed, so that the glossiness value was set at 80. Note that in FIG. **8A** that illustrates the height distribution, the checked pattern in the first area is not illustrated for convenience of illustration although the checked glossiness pattern, constituted by the nonglossy portions **84** and the glossy portions **85**, was formed also in the first area **81** as described above.

(100) The material of the mold used to mold the resin component **80** described with reference to FIGS. **8A** to **8C**, was stainless steel. First, the radius end mill was fixed to the machining center of FIG. **5** and the mold was roughly machined as described above, and then the surface of the mold was ground into a mirror surface by using the rotary grinder and diamond paste. Then, for forming the checked pattern constituted by the nonglossy portions **84** and the glossy portions **85**, an inverted shape for forming the convex portions **82**, the fine concave-and-convex structure, and the flat portions **83** was formed in the mold by using the ball end mill as illustrated in FIGS. **6** to **7**. After that, injection molding was performed by using the manufactured mold, for obtaining the resin component **80**. Note that the resin material used was a black HIPS, as an example.

(101) After that, a process was performed for giving a logo or the like to the first area **81** of the resin component. Since the difference in height between the nonglossy portions **84** and the glossy portions **85** was set at a small value in a range from 5 to 15 μm , the process was able to be performed stably.

(102) Then, the outer surface of the resin component **80** obtained in the present example was visually observed by a person with the normal eyesight, for evaluating whether the person can perceive any discontinuity (gap) of the design pattern in the boundary between the first area and the second area. As a result, although the results varied depending on angles at which the resin component was observed, it was confirmed that the boundary between the second area **87** and the first area **81** is inconspicuous. This is because the checked pattern as illustrated in FIG. **8B** is kept across the whole of the outer surface of the resin component **80**. In particular, it was confirmed that a visible gap and uncomfortable feeling for the boundary is significantly suppressed compared to a conventional resin component as illustrated in FIG. **2A**, in which no glossiness pattern is formed in the first area.

Example 2

(103) FIGS. **9A** to **9C** are diagrams for illustrating a resin component **80** of Example 2. FIG. **9A** illustrates a height distribution of an outer surface of the resin component **80**, FIG. **9B** illustrates a glossiness distribution of the outer surface of the resin component **80**, and FIG. **9C** illustrates a shape of a cross section in the vicinity of the outer surface of the resin component **80**.

(104) As illustrated in FIG. **9B**, the size and the pitch of a checked pattern of the present example are the same as those of Example 1 illustrated in FIG. **8B**. Example 2 differs from Example 1 in that a transition area **86** is formed between the first area **81** formed in a center portion and the second area **87** formed in a peripheral portion. As illustrated in FIG. **9A**, in the transition area **86**, the height of the convex portions **82** decreases monotonously as the transition area **86** extends in a direction from the second area **87** toward the first area **81**.

(105) Specifically, the transition area **86** was set at 28 mm (that is equivalent to four pitches of the checked pattern) in a longitudinal direction and in a lateral direction, and the height of the convex portions **82** was decreased by 10 μm every time the transition area **86** extends by 7 mm (that is equivalent to one pitch) in a direction from the second area **87** toward the first area **81**. In the first area **81**, the difference in height between the nonglossy portions **84** and the glossy portions **85** was set at 5 μm so as not to affect the process to give a logo or the like to the first area **81**. The difference in height is equal to the height of the fine concave-and-convex structure of the nonglossy portion **84** with respect to the flat surface of the glossy portion **85**. In the glossiness pattern, the convex portion or the fine concave-and-convex structure corresponds to the nonglossy portion **84**, and the flat portion **83** corresponds to the glossy portion **85**. The glossiness value of the nonglossy portion **84** was 30, and the glossiness value of the glossy portion was 80. As illustrated in FIG. 9B, the glossiness pattern constituted by the nonglossy portions **84** and the glossy portions **85** was formed across the whole of the surface including the first area **81** and the transition area **86**. A height structure in a side view, of the resin component including the first area **81**, the second area **87**, and the transition area **86** is illustrated in FIG. 9C. Note that in FIG. 9A that illustrates the height distribution, the checked pattern in the first area is not illustrated for convenience of illustration although the checked glossiness pattern, constituted by the nonglossy portions **84** and the glossy portions **85**, was formed also in the first area **81** as described above.

(106) The material of the mold was stainless steel. First, the radius end mill was fixed to the machining center of FIG. 5 and the mold was roughly machined as described above, and then the surface of the mold was ground into a mirror surface by using the rotary grinder and diamond paste. Then, for forming the checked pattern constituted by the nonglossy portions **84** and the glossy portions **85**, an inverted shape for forming the convex portions, the fine concave-and-convex structure, and the flat portions was formed in the mold by using the ball end mill as illustrated in FIGS. 6A, 6B, 7A, and 7B. After that, injection molding was performed by using the manufactured mold, for obtaining the resin component **80**. Note that the resin material used was a black HIPS, as an example.

(107) After that, a process was performed for giving a logo or the like to the first area **81** of the resin component. Since the difference in height between the nonglossy portions **84** and the glossy portions **85** was set at a small value of 5 μm , the process was able to be performed stably.

(108) Then, the outer surface of the resin component **80** obtained in the present example was visually observed by a person with the normal eyesight, for evaluating whether the person can perceive any discontinuity (gap) of the design pattern in the boundary between the first area and the second area. As a result, although the results varied depending on angles at which the resin component was observed, the glossiness pattern as illustrated in FIG. 9B was kept across the whole of the outer surface of the resin component **80**. In addition, it was confirmed that the boundary is more inconspicuous than the boundary in Example 1. This is because the height of the convex portions is changed step by step in a direction from the second area **87** toward the first area **81**.

Example 3

(109) In Example 2, the transition area **86** was formed between the first area **81** formed in a center portion and the second area **87** formed in a peripheral portion. In the transition area **86**, as illustrated in FIG. 9A, the height of the convex portions **82** decreases monotonously as the transition area **86** extends in a direction from the second area **87** toward the first area **81**.

Specifically, the transition area **86** was set at 28 mm (that is equivalent to four pitches of the checked pattern) in a longitudinal direction and in a lateral direction, and the height of the convex portions **82** was decreased by 10 μm every time the transition area **86** extends by 7 mm (that is equivalent to one pitch) in a direction from the second area **87** toward the first area **81**.

(110) In Example 3, like a so-called hairline pattern, a width of each concave or convex portion is small, and if the height between convex portions and concave portions is changed, the glossiness intensity changes accordingly.

(111) First, with reference to FIGS. **10A** to **10D**, an example of a structure of an outer surface **11** of a document cover will be described. FIG. **10A** illustrates the whole of the outer surface **11**. As in Example 2, the outer surface **11** includes a first area **81**, a second area **87** formed in a periphery of the first area **81**, and a transition area **86** formed between the first area **81** and the second area **87**. In the whole of the second area **87**, a hairline concave-and-convex structure having a predetermined height is formed. In the transition area **86**, six hairline areas having different heights between concave and convex portions are formed, and the height between concave and convex portions gradually decreases as the transition area **86** extends from the second area **87** toward the first area **81**. FIG. **10B** illustrates six hairline areas **21** to **26** formed in a local area **1001** of the transition area **86** and having different heights between concave and convex portions.

(112) As described above, in the hairline pattern in which a width of each concave or convex portion is small, the glossiness intensity changes in accordance with the height between concave and convex portions. Thus, in the present example, the glossiness intensity of the areas **21** to **26** also changes gradually. FIG. **10C** illustrates a cross section of the areas **21** to **26** of the transition area **86**, and FIG. **10D** illustrates a glossiness value distribution of the areas **21** to **26**.

(113) As illustrated in FIG. **10C**, the difference in height between concave and convex portions of the rough surface formed on the outer surface **11** is decreased almost linearly (for example, in accordance with a linear function) in the order of the area **21** the area **26**, in consideration of easiness of controlling the machining. Note that the resolution of concave and convex portions of the rough surface formed on the outer surface **11** may be defined as the number of convex portions (concave portions) formed per one inch, and that the number of convex portions (concave portions) is 30 (the width of one convex or concave portion is about 420 μm).

(114) In addition, the resolution is almost constant in the areas **21** to **26**.

(115) In a case where the width of each concave or convex portion is less than 1mm as in this example, when the height between concave and convex portions is changed, the glossiness of a macro area in which a group of the concave and convex portions is formed changes. That is, if the height between concave and convex portions is changed step by step in the areas **21** to **26**, the glossiness value of the areas **21** to **26** changes step by step. For example, if the glossiness value is measured by using a glossmeter that measures a 60° specular glossiness (JIS Z 8741), the glossiness value of the areas **21** to **26** often changes nonlinearly as illustrated in FIG. **10D**. That is, in the example illustrated in FIGS. **10A** to **10D**, although the difference in height between concave and convex portions of the rough surface formed on the outer surface **11** changes linearly (in accordance with a linear function), the glossiness value changes nonlinearly. Note that in FIG. **10B**, the difference in height between concave and convex portions of the rough surface decreases in a direction from the left deep-color area **21** toward the right light-color or white-color area **26**. In such a structure, bottom surfaces of the concave and convex portions that are flat portions are more exposed as the bottom surfaces are located farther from the left deep-color area **21** and closer to the right light-color or white-color area **26**. Thus, the light reflected off from the bottom surfaces increases, and is perceived by an observer as larger glossiness.

(116) However, if the glossiness changes nonlinearly on the outer surface **11** of the resin component in a direction from the second area toward the first area in which a logo or the like is to be formed, an observer may not sufficiently perceive the effect in design, in terms of smoothness. Note that the width of each of the areas **21** to **26** of the rough surface formed on the outer surface **11** (that is, a size of each of the areas in an arrangement direction that is a right-left direction in FIG. **10B**) is at least larger than about 10 mm. If the width of each of the areas **21** to **26** of the rough surface formed on the outer surface **11** is less than about 10 mm, observers will hardly identify the difference in height of a rough surface of each area, even if they compare the difference in height of one area with the difference in height of an adjacent area.

(117) FIGS. **11A** to **11D** are diagrams for illustrating a resin component of Example 3. The forms of FIGS. **11A** to **11D** are the same as those of FIGS. **10A** to **10D**. FIG. **11A** illustrates the whole of the

outer surface **11**. FIG. **11B** illustrates six hairline areas **31** to **36** formed in a local area **1001** of a transition area **86** and having different heights between concave and convex portions. As illustrated in FIG. **11D**, the glossiness value of the areas **31** to **36** changes linearly in a direction from the area **31** toward the area **36**. Thus, the height of the hairline concave-and-convex structure, which forms the areas **31** to **36**, changes nonlinearly in the direction from the area **31** toward the area **36**.

(118) Note that as in FIG. **9C**, the glossiness intensity represented by the vertical axis of the graph of FIG. **11D** was measured by using a glossmeter, which is designed to measure a specular glossiness at a reflection angle of 60 under JIS Z 8741. For example, the measurement values on glossiness can be obtained by using a certain glossmeter, such as a handy type gloss meter PG-1 (product name) made by NIPPON DENSHOKU INDUSTRIES CO. LTD. Specifically, the measurement values on glossiness can be obtained by setting the reflection angle at 60°, and pressing a measurement switch in a state where a photometer of the glossmeter is pressed against a glossy portion of the molded product.

(119) Thus, the resin component of Example 3 is molded such that the glossiness value changes uniformly (linearly) in the direction from the second area toward the first area in which a logo or the like is to be formed. Note that in FIG. **11C**, the width of each of the areas **31** to **36** (glossy portion) that are rough surfaces having different differences in height (that is, a size of each of the areas in an arrangement direction of the areas that is a right-left direction in FIG. **11C**) is at least larger than 10 mm. In addition, it is preferable that the widths of the areas be made almost equal so that the change in glossiness value of the areas perceived by observers becomes as uniform as possible.

(120) As described above, in the resin component of Example 3, the height of the convex portions of each area with respect to the flat portions is determined such that the glossiness value of the transition area changes linearly. In such a resin component, since the glossiness intensity changes linearly in a direction from the first area to the second area of the outer surface **11**, the discontinuity (gap) of the design pattern can be reduced.

(121) Note that the material of resin components manufactured by using a mold may be a resin, such as ABS or HIPS (high impact polystyrene), but the type of the resin is not intended to limit the present invention.

(122) Method of Manufacturing Injection Molding Mold

(123) The resin component of the present example has a plurality of areas formed on a surface of the resin component and having rough surfaces with different differences in height between concave and convex portions. The resin component is formed through injection molding that uses a mold. When the injection molding mold used for the purpose is manufactured, a size of a cutting portion of a cutting tool used to form rough surfaces on the mold surface and a glossiness value given to a certain area of the plurality of areas by the mold are used to control depth of cut of the mold. That is, the depth of cut performed by the cutting tool when a mold surface corresponding to the certain area is cut is controlled in accordance with the size of the cutting portion and the glossiness value given to the certain area. More specifically, the below-described control for machining the mold uses glossiness control information (glossiness map information) in which the size of the cutting portion, the cutting resolution by the cutting tool, and the glossiness value of the outer surface of the resin component produced by cutting the mold are associated with each other.

(124) The injection molding mold in Example 3 is manufactured by using the machining center illustrated in FIG. **5** and described in the first embodiment. Since the first mold-machining process described with reference to FIG. **6A** and the second mold-machining process as described with reference to FIG. **6B** are the same as those of the first embodiment, the description thereof will be omitted.

(125) FIG. **12A** illustrates a third machining process to manufacture a mold **93** of Example 3, and FIG. **12B** illustrates a relationship between the cut of depth and the glossiness value in the third machining process.

(126) As illustrated in FIG. 12A, in the third machining process, the ball end mill **106** is used as a cutting tool, and a surface **101** of the mold **93** is cut for forming concave portions that are to be transferred to the resin component as convex portions. In the third machining process, the surface **101** of the mold **93** is cut and scanned while the ball end mill **106** is rotated, so that concave portions **1601** to **1606** are formed. The concave portions **1601** to **1606** respectively correspond to convex portions formed in the areas **36** to **31** of the resin component. Note that FIG. 12A illustrates only one concave portion in each area for simplifying illustration. The concave portions have different depth, and are to be transferred to the resin component for forming convex portions of the areas **31** to **36**. In practice, however, each of the concave portions **1601** to **1606** is constituted by many concave portions formed in a corresponding area at a predetermined resolution.

(127) The material of the mold **93**, which is to be machined as described above, is preferably stainless steel for the machinability and durability required in injection molding, but may be another material, such as brass or steel.

(128) In the following description, an example of a method of determining the amount of movement of the cutting tool (e.g. ball end mill **106**) in the Z direction in the above-described third machining process, that is, an example of a method of determining the depth of cut of the concave portions **1601** to **1606** will be described. The depth of cut of concave portions of each area is determined, associated with the glossiness given to a corresponding area of the outer surface **11** of the resin component.

Example 1 of Manufacturing Mold

(129) In Example 1 of manufacturing the mold, a Z-direction-movement-amount determination process performed in the machining center of FIG. 5 depending on the NC data **99** is executed by a control system and a control program. The control system constitutes a control device **92** and mainly includes a CPU, and the control program is a program to control the control system. FIG. 13 illustrates an example of a specific configuration of the control device **92** of FIG. 5.

(130) The control system of FIG. 13 includes a CPU **601** serving as a main control means, a ROM **602** serving as a storage device, and a RAM **603**. The ROM **602** can store the control program, information on constants, and the like. The control program is used for the CPU **601** to achieve later-described manufacturing procedures. The above-described NC data **99** (FIG. 4) and a table data, especially such as a later-described glossiness map, can be stored in the ROM **602**. The RAM **603** is used as a work area used by the CPU **601** when the CPU **601** executes the control procedures. Note that the control program of the CPU **601** for achieving the later-described control procedures may be stored in an external storage device, such as an HDD or an SSD (both not illustrated), or a storage portion (e.g. EEPROM area) of the ROM **602**.

(131) In this case, the control program of the CPU **601**, which achieves the later-described control procedures, can be supplied to the above-described storage portion via a network interface **606** for example; and can be updated with a new (another) program. The network interface **606** used to communicate via a network **607** may operate on communication standards on wire communications, such as IEEE 802.3, or on communication standards on wireless communication, such as IEEE 802.11 or 802.15.

(132) Alternatively, the control program of the CPU **601**, which achieves the later-described control procedures, may be supplied to the above-described storage portion via a storage means, such as one of various magnetic disks, an optical disk, or a flash memory, and a driving device that drives the storage means; and may be updated. The storage means or the storage portion that stores the control program of the CPU **601**, which achieves the later-described control procedures, is a computer-readable storage medium that stores the control procedures for implementing the present invention. In addition, although not essential, a UI device (user interface device) may be connected to the control system of FIG. 13. The UI interface may be a terminal such as a handy terminal, or a device such as a keyboard, a display, a jog dial, or a pointing device (or a control terminal including those devices).

(133) Driving portions for the cutting tool **94** of the machine body **91** of FIG. **5**, such as the spindle **95**, the X stage **96**, the Y stage **97**, and the Z stage **98**, are controlled via a driver **605** of FIG. **13**. For example, the CPU **601** controls the above-described portions of the machine body **91** by changing driving control data given to the driver **605** via the interface **604**. The CPU **601** determines and controls the number of rotations of the cutting tool **94** (e.g. ball end mill illustrated in FIG. **6A**) and the amount of movement of the cutting tool **94** in the Z direction, that is, the depth of cut of the concave portions **1601** to **1606**.

(134) FIG. **14** illustrates a functional configuration of the control device **92** configured as in FIG. **13**. The functional block of FIG. **14** is achieved by software executed by the CPU **601** on the hardware of the control system of FIG. **13**. For example, the functional block is executed by a movement-amount determination program **701** that determines the amount of movement of the cutting tool **94** in the Z direction.

(135) In FIG. **14**, the movement-amount determination program **701** includes a glossiness-map input portion **702**, a ball-end-mill information input portion **703**, a movement-amount calculation portion **704**, a ball end mill database **705**, and a data output portion **706**.

(136) Hereinafter, an operation of the movement-amount determination program **701** of FIG. **14** will be described with reference to the flowchart of FIG. **15**. The control procedures of FIG. **15** are processes to create a depth-of-cut map that is outputted via the data output portion (depth-of-cut map output portion) **706**, to control the machine body **91**. The depth-of-cut map has information on a depth of cut in the Z direction, which is set at a corresponding pixel position of a glossiness map **9** of FIG. **16**. The function of the data output portion **706** corresponds to the function of the interface **604** and the driver **605** of FIG. **13**, as an example. In the actual cutting control, the CPU **601** reads information on a depth of cut in the Z direction, which is set at a corresponding pixel position, depending on a value stored in the depth-of-cut map created in the procedures of FIG. **15**. Then the CPU **601** produces driving information for controlling each portion of the machine body **91** by using the depth of cut, and outputs the driving information to each portion of the machine body **91** via the interface **604** and the driver **605**.

(137) In the loop of Step **S801** to Step **S803** of FIG. **15**, the CPU **601** two-dimensionally scans the glossiness map **9**, and calculates a depth of cut for each pixel, from a corresponding glossiness value. In Step **S801**, the CPU **601** obtains the glossiness map **9** from the glossiness map input portion. The glossiness-map input portion **702** has a function that reads a glossiness map as illustrated in FIG. **16**, from the ROM **602** of FIG. **13**, an external storage device (not illustrated), or a server on the network **607**, and loads the glossiness map to the movement-amount determination program **701**.

(138) The glossiness map **9** of FIG. **16** may be image data, and may be formed in a data format similar to the bit map. The glossiness map **9** contains many pixels **191**, as elements, each corresponding to a certain position of the outer surface **11** of the resin component. For example, a pixel **191** has glossiness data that is represented by using 8 bits and has a value from 0 to 100. The glossiness map **9** has data produced in accordance with the design of the outer surface of a certain resin component molded by using the mold **93**, in particular, in accordance with a glossiness value distribution of each of the areas (**31** to **36**, . . .) of the outer surface of the resin component. That is, the glossiness value of each pixel **191** is determined in design in accordance with the glossiness value given to a corresponding position of the outer surface **11** of the resin component molded by using the mold **93**. Note that in FIG. **16**, although the glossiness map **9** is a two-dimensional map having a rectangular area for simplification, the glossiness map **9** in a practical use has a data configuration determined in accordance with the shape of an outer surface of a certain resin component.

(139) In Step **S802** of FIG. **15**, the movement-amount calculation portion **704** calculates a depth of cut at a pixel position (x, y) of the glossiness map **9** in accordance with a glossiness value given to the pixel position (x, y). In this step, the movement-amount calculation portion **704** uses the ball-

end-mill data that is cutting tool information, performs interpolation if necessary, and calculates the depth of cut at the pixel position (x, y).

(140) FIG. 17 illustrates one example of the ball-end-mill data, which is cutting tool information. The cutting tool information (ball-end-mill data) of FIG. 17 contains glossiness value associated with the depth of cut performed by a cutting tool. The glossiness value is also associated with the resolution of concave portions formed by cutting a mold, and with the bit diameter of the cutting tool. The ball-end-mill data, which is cutting tool information, is created in advance by using a ball end mill having various bit diameters and conducting an experiment. In the experiment, a mold is cut so as to have various depths, a resin component is molded through injection molding, and a glossiness value of an outer surface of the resin component is measured by using a glossmeter.

(141) Note that in FIG. 17, although values in a range between 100 and 1200 dpi are not illustrated, it is preferable that the values be stored in this range, in accordance with a resolution and a cutting tool that would be used in a mold manufacturing process. In addition, although FIG. 17 indicates only the values in the depth of cut of 0.005 (5 μm), 0.02 (20 μm), 0.05 (50 μm), 0.1 (100 μm), 0.2 (200 μm), it is preferable that other data be stored by performing the measurement on a depth of cut that would be used in a mold manufacturing process. In addition, for a case where the CPU 601 cannot find data, in the tool information of FIG. 17, that corresponds to a certain depth of cut, the CPU 601 can calculate an approximate value from an appropriate data range, or calculate a desired depth-of-cut value by performing interpolation.

(142) In Step S803 of FIG. 15, the CPU 601 determines whether the CPU 601 has calculated the depth of cut for all the pixel positions of the glossiness map 9. If the CPU 601 determines that the CPU 601 has calculated the depth of cut for all the pixel positions, then the CPU 601 ends the depth-of-cut map creation process of FIG. 15. If the CPU 601 determines that the CPU 601 has not calculated the depth of cut for all the pixel positions, then the CPU 601 changes a pixel position, and returns to Step S801 for repeatedly performing the above-described processes.

(143) By molding the resin component with the mold having a mold surface that is cut in the above-described manner, the areas (31 to 36 . . .) of the outer surface 11 of the resin component can be given the glossiness (glossiness value distribution: glossiness pattern) that changes linearly, as illustrated in FIG. 11D. For example, suppose that the glossiness map 9 is given, which has a glossiness value distribution (glossiness pattern) as illustrated in FIG. 11D, and which corresponds to the areas (31 to 36 . . .) of the outer surface 11 of a certain resin component. Through the above-described procedures or processes, the CPU 601 allows the mold surface to be cut, depending on the glossiness map 9 and with reference to the ball-end-mill data that is cutting tool information. In this operation, the mold surface is cut so as to produce a depth-of-cut distribution that can form the difference in height between concave and convex portions of the areas (31 to 36 . . .) as illustrated in FIG. 11B.

(144) Thus, in the resin component molded with the manufactured mold, the rough surfaces of the plurality of areas 31 to 36 have different differences in height such that the glossiness value of adjacent areas changes linearly in the arrangement direction in which the areas 31 to 36 of the outer surface 11 are arranged. As described above, in such a resin component, the uniformity in the amount of change of glossiness on the outer surface 11 is kept, and the glossiness value changes smoothly in the direction in which the plurality of areas is arranged. Thus, under the control by the first embodiment, a resin component having a new and good design can be provided.

(145) In addition, the design of an electronic device, such as a printer of FIG. 1, including such a resin component as one portion of an exterior component can be significantly improved.

Example 2 of Manufacturing Mold

(146) In Example 1 of manufacturing a mold, the description has been made for a basic method that calculates the depth-of-cut map with reference to the glossiness map 9 of FIG. 16 and the ball-end-mill data of FIG. 17, which is cutting tool information. However, there may be a case in which the specifications including the bit diameter of the ball end mill, which can be made for cutting a mold

on various manufacturing conditions, are fixed and cannot be changed. In such a case, a depth of cut to achieve a desired glossiness may not be obtained, for example, due to a relationship between the inputted resolution and the drill diameter of the ball end mill. As countermeasures, in Example 2 of manufacturing a mold, the description will be made for an example of control that reconfigures glossiness values of the glossiness map, which are created under a condition on cutting tools that can be or should be used, the cutting tool information, and a desire from a designer.

(147) In the present example of manufacturing a mold, the control system necessary for the Z-direction-movement-amount determination process performed depending on the NC data **99**, and the function and the configuration of the control system are the same as those described with reference to FIGS. **13** and **14**. In the present example of manufacturing a mold, the control procedures of the movement-amount determination program **701** may be performed as illustrated in FIG. **18**. Similar to the control procedures of FIG. **15**, the control procedures of FIG. **18** are processes to create a depth-of-cut map that is outputted via the data output portion **706**, to control the machine body **91**.

(148) In Step **S1101** of the flowchart of FIG. **18**, the CPU **601** obtains the glossiness map **9** (FIG. **16**) and the ball-end-mill data (FIG. **17**), which is cutting tool information, from the glossiness-map input portion **702**.

(149) Next, in Step **S1102**, the CPU **601** obtains a maximum value GM_{max} and a minimum value GM_{min} from glossiness values stored in the glossiness map **9**. Hereinafter, a maximum glossiness value of the ball-end-mill data (FIG. **17**) is denoted by GB_{max} , a minimum glossiness value of the ball-end-mill data is denoted by GB_{min} , a corrected maximum glossiness value is denoted by GC_{max} , and a corrected minimum glossiness value is denoted by GC_{min} . In addition, an uncorrected glossiness value is denoted by G_{in} , and a corrected glossiness value is denoted by G_{out} . As initial values, the CPU **601** sets GM_{max} to the corrected maximum glossiness value GC_{max} , and GM_{min} to the corrected minimum glossiness value GC_{min} .

(150) In Step **S1103**, the CPU **601** compares the maximum glossiness value GB_{max} of the ball-end-mill data and the maximum glossiness value GM_{max} of the inputted glossiness values.

(151) Then the CPU **601** proceeds to Step **S1104** if the maximum glossiness value GM_{max} of the ball-end-mill data is smaller than the maximum glossiness value GM_{max} , or proceeds to Step **S1105** if not. In Step **S1104**, the CPU **601** sets the maximum glossiness value GB_{max} to the corrected maximum glossiness value GC_{max} .

(152) In Step **S1105**, the CPU **601** compares the minimum glossiness value GB_{min} of the ball-end-mill data and the minimum glossiness value GM_{min} of the inputted glossiness values.

(153) Then the CPU **601** proceeds to Step **S1106** if the minimum glossiness value GM_{min} of the ball-end-mill data is larger than the minimum glossiness value GM_{min} , or proceeds to Step **S1107** if not. In Step **S1106**, the CPU **601** sets the minimum glossiness value GB_{min} to the corrected minimum glossiness value GC_{min} .

(154) In the loop of Step **S1107** to Step **S1109**, the CPU **601** two-dimensionally scans the glossiness map **9**, and calculates a depth of cut of each pixel from a corresponding glossiness value. First, in Step **S1107**, the CPU **601** uses an equation (1), and corrects and converts an inputted glossiness value of a pixel.

$$(155) \quad G_{out} = (G_{in} - GM_{min}) \times \frac{GC_{max} - GC_{min}}{GM_{max} - GM_{min}} + GC_{min} \quad (1)$$

(156) The equation (1) changes a range between the maximum glossiness value and the minimum glossiness value of the glossiness map **9** in accordance with the maximum glossiness value and the minimum glossiness value obtained from the cutting tool, and corrects the glossiness value information of a certain pixel in accordance with a scaling factor. In Step **S1108**, the CPU **601** calculates a depth of cut by using a glossiness value obtained at a pixel position (x, y) and corrected in Step **S1107** and the ball-end-mill data, and by performing interpolation.

(157) In Step **S1109**, the CPU **601** determines whether the CPU **601** has calculated the depth of cut

for all the pixel positions of the glossiness map **9**. If the CPU **601** determines that the CPU **601** has calculated the depth of cut for all the pixel positions, then the CPU **601** ends the depth-of-cut map creation process of FIG. **18**. If the CPU **601** determines that the CPU **601** has not calculated the depth of cut for all the pixel positions, then the CPU **601** changes a pixel position, and returns to Step **S1107** for repeatedly performing the above-described processes.

(158) In the above-described manner, the CPU **601** corrects the glossiness value of each pixel of the glossiness map **9** in accordance with the maximum glossiness value and the minimum glossiness value obtained from the cutting tool, and creates a depth-of-cut map that contains depth-of-cut values from which the corrected glossiness values can be obtained. Thus, the CPU **601** compresses the range of glossiness values of the glossiness map **9**, depending on the limitation of a cutting tool to be used; and can create the depth-of-cut map that contains depth-of-cut values and provides a glossiness value distribution (glossiness pattern) that the cutting tool can handle.

(159) For example, it can be prevented that the range of glossiness value of the glossiness map **9** becomes larger than the range of glossiness value limited by a cutting tool, and that the glossiness value reaches a maximum/minimum value inside an edge portion of the outer surface of a resin component in which the areas (**31** to **36**) are formed by the mold that has been cut. Thus, it is possible to manufacture the mold that can give a glossiness value distribution to the outer surface of the resin component within a range of glossiness value that the cutting tool can handle. The glossiness value distribution is made similar to the whole impression of the glossiness value distribution of the glossiness map **9**.

(160) FIGS. **19A** and **19B** illustrate one example of a resin component molded with a mold manufactured by the above-described mold machining control. On the outer surface of the resin component used as the document cover **12**, areas **1201** to **1206** that correspond to the areas **31** to **36** of the outer surface **11** of the resin component of FIG. **11A** are disposed. FIG. **19A** illustrates a glossiness distribution of the areas **1201** to **1206**. FIG. **19B** illustrates side surfaces of the areas **1201** to **1206** so that the difference in height of the rough surfaces (concave and convex portions) formed by transferring concave portions of the mold can be seen. In the example illustrated in FIGS. **19A** and **19B**, the areas with rough surfaces having different differences in height and formed by transferring the concave portions of the mold to a plate-like resin component having a thickness of 16 mm, that is, the areas **1201** to **1206** having different glossiness values are arranged.

(161) Note that the ball end mill and the cutting tool information, which were used for molding the resin component of FIG. **19**, are the same as those of FIG. **17**. The ball end mill was used for cutting a mold, and the cutting tool information stored glossiness values. In the example of FIG. **19**, the resolution was 100 dpi, and the bit diameter of the cutting tool (ball end mill) used for cutting the mold was 0.2 mm. In addition, the width (arrangement pitch) of each of the areas **1201** to **1206** in the arrangement direction was 60 mm.

(162) The glossiness map of the areas **1201** to **1206** of FIG. **19A** is set in a range from 30 to 80 (in steps of 10). In addition, by referring to the cutting tool information as illustrated in FIG. **17**, a desired glossiness value, which is set in the glossiness map, can be obtained by selecting a depth of cut of the mold as follows. For example, in the area **1201**, the glossiness value was controlled into 30 by selecting a depth of cut of 38 μm . In the area **1202**, the glossiness value was controlled into 40 by selecting a depth of cut of 30 μm . In the area **1203**, the glossiness value was controlled into 50 by selecting a depth of cut of 23 μm . In the area **1204**, the glossiness value was controlled into 60 by selecting a depth of cut of 16 μm . In the area **1205**, the glossiness value was controlled into 70 by selecting a depth of cut of 10 μm . In the area **1206**, the glossiness value was controlled into 80 by selecting a depth of cut of 5 μm .

(163) The material of the mold was stainless steel. First, the radius end mill was fixed to the machining center of FIG. **5** and the mold was roughly machined as described with reference to FIG. **6A**, and then the surface of the mold was ground into a mirror surface by using the rotary grinder and diamond paste as described with reference to FIG. **6B**. Then, an inverted shape for a step

pattern of the areas **1201** to **1206** of FIG. **19** was formed on the mold by using the ball end mill. After that, injection molding was performed by using the manufactured mold, for forming the resin component having the above-described glossiness value distribution. The resin material used for the injection molding was a black HIPS.

(164) Then, the outer surface of the resin component obtained as described above was visually observed by a person with the normal eyesight, for evaluating a gap in glossiness between steps. As a result, it was confirmed that the gap is inconspicuous on the outer surface of the manufactured resin component. Thus, the result was good because the glossiness value changes linearly in the areas **1201** to **1206** of the manufactured resin component, that is, because a difference in glossiness value between adjacent ones of the areas **1201** to **1206**, which have an identical width, is kept constant.

(165) In the example of FIG. **19**, the difference in glossiness value between adjacent ones of the areas **1201** to **1206**, which give different glossiness values, is 10. However, the difference in glossiness value between adjacent ones of the areas **1201** to **1206** may have any value. In addition, in Example 3, it is perceived that the difference in glossiness value between adjacent areas changes almost linearly. In the above-described machining control, however, the difference in glossiness value between adjacent areas may change in any different manner, not linearly.

(166) In addition, the cutting tool information of FIG. **17** is information on the glossiness value obtained from a certain bit diameter of the ball-end-mill data and the depth of cut, and the information on the glossiness value is formed as a data table stored in a memory. However, such cutting tool information may not be formed as a data table. For example, the cutting tool information may be expressed by the following equation (2), which is one example of a function (equation).

$$(167) \quad G(D, ap) = G \times \left(1 - \frac{\times 4 \times ap(D - ap)}{25.4 \div rez \times 25.4 \div rez}\right) \quad (2)$$

(168) In the equation (2), D is a bit diameter of the cutting tool, ap is a depth of cut, rez is a resolution of concave portions formed by cutting (or projections of a molded resin component), and G is a glossiness value of the mold **93** having been ground into a mirror surface (FIG. **6B**). The equation (2) that expresses the glossiness value G (D,ap) is a function expression that expresses how much the glossiness value G decreases when the concave portions are formed by cutting a mirror surface of the material of the mold **93** having the glossiness value G, and when the shape of the mold is transferred to the resin component so as to form cylindrical projections on the resin component.

(169) The above description has been made for a rough surface in which projections (or concave portions in a mold surface) having the same shape are arranged corresponding to pixels of the glossiness map. However, the rough surface formed on the outer surface of the resin component may not have the simple structure that has the above-described projections. For example, the rough surface may be constituted by units, and each unit may correspond to a plurality of pixels of the glossiness map and have a few or a few tens of projections and concave portions arranged in a predetermined matrix and having different heights and depths. In this case, not only the projections but also the concave portions may be used and combined with each other such that a total glossiness value of the plurality of pixels becomes identical. With such a structure, the glossiness can be controlled with a high degree of flexibility, by using patterns having different spatial frequencies.

(170) The present invention may be achieved by supplying a program that executes one or more functions of the above-described examples, to a system or device via a network or a storage media, and by causing one or more processors of a computer of the system or the device to read and execute the program. Alternatively, the present invention may be achieved by a circuit (for example, ASIC) that executes the one or more functions.

(171) In the above-described first embodiment and examples, the description has been made as an

example for the surface pattern in which the nonglossy portions are associated with the convex portions and the glossy portions are associated with the flat portions. However, the configuration of the surface pattern, such as the relationship between the glossiness and the concave or convex portions, is not limited to the above-described structure. For example, inversely to the above description, the nonglossy portions may be associated with the flat portions and the glossy portions may be associated with the convex portions in accordance with an intended design. In this case, the resin component will be manufactured such that the fine concave-and-convex structure is formed on each flat portion, for example.

(172) Even in this case, on the outer surface of a resin component including the first area and the second area, a surface pattern in which areas with different optical properties are arranged under a specific rule is formed continuously in the first area and the second area. The resin component is formed such that the difference in height between areas with different optical properties in the surface pattern of the first area is smaller than the difference in height between areas with different optical properties in the surface pattern of the second area.

(173) In addition, in the above-described first embodiment and examples, the design pattern, the glossiness pattern, or the concave and convex pattern is formed such that a unit area with the same size and the same shape is repeatedly disposed across the whole surface of the resin component. However, unit areas of the pattern may not necessarily be the same as each other. Since the present invention has been made for solving the problem on the difference in height of the surface pattern that affects the process to give a logo or the like to the first area, the present invention can also be applied for pattern arrangements having different spatial frequencies. For example, the spatial frequency of the glossy-pattern arrangements may be higher than the spatial frequency of the nonglossy-pattern arrangements. In such a structure, a visible gap on a boundary between an area having a large difference in height and an area having a small difference in height can be effectively reduced. This is because patterns with a high frequency attracts an observer more than patterns with a low frequency.

(174) In addition, in the above description, a hot stamping is performed as a process to give a logo or the like to a resin component having a design pattern in which the areas with different optical properties are arranged. However, the process for numerals, characters, a figure, or a logo may be performed by using any method, other than the hot stamping, such as printing, painting, or attaching an information bearing member such as a seal or a sticker. However, if the outer surface of the resin portion has a large difference in height, the process may fail to produce a good result. Thus, when the process is performed by using any other method, the process will produce a good result if the maximum difference in height in the first area is set at a value, such as 50 μm or less, that allows the process to be performed stably.

(175) In addition, although the mold used to mold the resin component is manufactured through the cutting process, the method of machining the mold is not limited to this. For example, the mold may be manufactured by using another method, such as a method using a laser beam machine. In addition, the injection molding that uses a mold may not necessarily be used for forming a resin component of the present invention. For example, the resin component may be manufactured by using a resin material and three-dimensionally forming areas with different optical properties through a 3D printing technology.

Second Embodiment

(176) In a second embodiment, a product of the present invention includes a curved-surface portion. A component identical to a component of the first embodiment will be omitted, and different features will be mainly described.

(177) FIGS. 22A and 22B illustrate an outer surface **2011** of a conventional document cover. FIG. 22A illustrates the whole of the outer surface **2011**, and FIG. 22B illustrates a cross section of a portion of FIG. 22A, indicated by a broken line. The outer surface **2011** of FIG. 22A includes a flat-surface portion **2030** (first portion) and a curved-surface portion **2031** (second portion) that

surrounds four sides of the flat-surface portion **2030**. The curved-surface portion **2031** is the second portion that is inclined with respect to the flat-surface portion **2030**.

(178) The surface pattern of the flat-surface portion **2030** of FIG. **22A** is a surface pattern, such as a checked pattern, that is arranged under a specific rule. The surface pattern has a concave-and-convex structure in which convex portions formed when the outer surface **2011** is injection-molded is arranged under a specific rule. The concave-and-convex structure corresponds to convex portions **2041** illustrated in black color in FIG. **22B** and concave portions (flat portions) **2042** illustrated in white color. As illustrated in FIGS. **22A** and **22B**, the concave-and-convex structure is formed on the whole of the flat-surface portion **2030** for the design and functionality. Although it is preferable in design that a surface pattern which is the same as the surface pattern, including the convex portions **2041** and the flat portions **2042** of the flat-surface portion **2030** and having a regular difference in height, be continuously formed also in the curved-surface portion **2031**, the surface pattern is not formed in the curved-surface portion **2031** in a conventional configuration.

(179) This is because if the same surface pattern including the convex portions **2041** and the flat portions **2042** was formed also in the curved-surface portion **2031**, an undercut would be highly likely formed. The undercut will prevent the mold from being released in a mold releasing direction (i.e. upward direction in FIG. **22B**), in the injection molding. Thus, in the conventional configuration, the surface pattern having the concave-and-convex structure is not formed on the curved-surface portion **2031**. As a result, the continuity of the surface pattern that serves as a decorative surface is lost at the boundary between the flat-surface portion **2030** and the curved-surface portion **2031**, causing a visible gap and deteriorating the design.

(180) In contrast, the present embodiment provides a structure that allows the continuity of the surface pattern, which serves as a decorative surface, across the flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion). The flat-surface portion **2030** is a portion in which the mold releasing direction is equal to a direction in which a normal line extends, and the curved-surface portion **3031** is a portion which is inclined with respect to the flat-surface portion **2030**. In the present embodiment, the surface pattern formed on the outer surface **2011** of the resin component and serving as a decorative surface is a combination of a concave-and-convex pattern having a difference in height and a glossiness pattern. The glossiness pattern is an arrangement in which the areas having different optical properties are arranged under a specific rule.

(181) FIG. **23A** illustrates an outer surface **2011** of the present embodiment. FIG. **23A** illustrates the whole of the outer surface **2011**, and FIG. **23B** illustrates a cross section of a portion of FIG. **23A**, indicated by a broken line. As illustrated in FIGS. **23A** and **23B**, the outer surface **2011** of the present embodiment includes a flat-surface portion **2030** (first portion) and a curved-surface portion **2031** (second portion) inclined with respect to the flat-surface portion **2030**.

(182) Both of the flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion) have a glossiness pattern including less-glossy portions **2051** having a first optical property and glossy portions **2052** having a second optical property. The flat-surface portion **2030** (first portion) has a concave-and-convex pattern in which convex portions **2041** are arranged under a specific rule. In the present embodiment, the surface pattern is a pattern in which the glossiness pattern and the concave-and-convex pattern are combined (associated) with each other, for example. Specifically, as illustrated in FIG. **23B**, in the flat-surface portion **2030** (first portion), a less-glossy portion **2051** is formed on the top portion (upper surface) of a corresponding convex portion **2041**, and a glossy portion **2052** is formed on a corresponding flat portion **2042**. That is, in the present embodiment, the specific rule for arranging the areas having the first optical property and the areas having the second optical property is equal to the specific rule for arranging the concave-and-convex pattern. In addition, the convex portions **2041** are either one of the areas having the first optical property and the areas having the second optical property. However, the present disclosure is not limited to this. For example, the arrangement pattern of the convex

portions may be different from a design pattern in which the areas having different optical properties are arranged. Specifically, the arrangement pattern of the convex portions may be different from a pattern determined under the specific rule that arranges the areas having the first optical property and the areas having the second optical property.

(183) The less-glossy portion **2051** has a fine concave-and-convex structure that is formed on a surface of the less-glossy portion **2051** for scattering incident light, and that is difficult to visually recognize. The glossy portion **2052** has a smooth surface that specularly reflects incident light. That is, the less-glossy portion **2051** and the glossy portion **2052** are formed by giving different surface roughness values to the outer surface **2011** of the resin component. That is, in the present embodiment, as illustrated in FIG. 23B, the flat-surface portion **2030** (first portion) includes the convex portion **2041** having the fine concave-and-convex structure formed on the top surface of the convex portion **2041** and the flat portion **2042** having a smooth surface. The flat portion **2042** is a base surface of the flat-surface portion **2030** (first portion).

(184) On the other hand, the curved-surface portion **2031** (second portion) also has less-glossy portions **2051** and glossy portions **2052**. Each of the less-glossy portions **2051** has a fine concave-and-convex structure, and the less-glossy portions **2051** and the glossy portions **2052** are disposed in the same pattern. For example, each less-glossy portion **2051** is formed on the top portion of a corresponding convex portion whose height is lower than that of the convex portion **2041** of the flat-surface portion **2030** (first portion). The glossy portion **2052** is a base surface of the curved-surface portion **2031** (second portion).

(185) In the flat-surface portion **2030** (first portion) illustrated in FIG. 23B, a mold releasing direction (R) of the resin component is equal to a normal line (H). Since the curved-surface portion **2031** (second portion) is inclined with respect to the flat-surface portion **2030** (first portion), a normal line (H) at a certain position on the base surface is inclined with respect to the normal line R (H) of the flat-surface portion **2030** (first portion).

(186) Both in the flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion), the less-glossy portions **2051** and the glossy portions **2052** are formed such that they give a similar visual impression when viewed from respective normal (front) directions to the surfaces. For example, the flat-surface portion **2030** (first portion) is formed such that a direction in which the less-glossy portions **2051** of the flat-surface portion **2030** project from the glossy portions **2052** is equal to a normal line to the base surface of the flat-surface portion **2030** (first portion). Similarly, the curved-surface portion **2031** (second portion) is formed such that a direction in which the less-glossy portions **2051** of the curved-surface portion **2031** project from the glossy portions **2052** is equal to a normal line to the base surface of the curved-surface portion **2031** (second portion). With this structure, when each surface is visually recognized in a corresponding normal (front) direction, the observer (user) will perceive a regular pattern (such as a checked pattern) that gives almost identical visual impression.

(187) In the structure of the present embodiment illustrated in FIGS. 23A and 23B, unlike the conventional structure illustrated in FIGS. 22A and 22B, the surface (glossiness) pattern constituted by the less-glossy portions **2051** and the glossy portions **2052** is formed also on the curved-surface portion **2031**. Thus, in the present embodiment, the curved-surface portion **2031** (second portion) has the concave-and-convex structure with a minimum difference in height, which is required to sufficiently form the less-glossy portion **2051**. That is, the difference in height of the curved-surface portion **2031** (second portion) in the normal direction, which will cause an undercut acting in the mold releasing direction (i.e. upward direction in FIG. 23B), is smaller than the difference in height of the flat-surface portion **2030** (first portion) in the normal direction. Consequently, a molded resin component can be released from a mold with good mold releasability, and the resin component is not damaged when the resin component is released from the mold.

(188) In the structure illustrated in FIGS. 23A and 23B, it is preferable that the convex portions **2041** of the flat-surface portion **2030** project from the flat portions **2042**, which are a base surface

of the flat-surface portion **2030**, by a value in a range equal to or larger than 40 μm and smaller than 500 μm . The reason is that if the convex portions **2041** project by more than 40 μm , the molded product can have soil resistance against fingerprints, and that if the convex portions **2041** project by a value equal to or larger than 500 μm , a visible portion of the glossy portions becomes small at a certain angle, possibly impairing a sense of high quality. That is, in the present embodiment, it is preferable that the difference in height between the glossy portions **2052** and the less-glossy portions **2051** be equal to or larger than 40 μm and smaller than 500 μm .

(189) Note that in a later-described example (FIGS. **25** and **26**), convex portions **2083** corresponding to the above-described convex portions **2041** project by about 50 μm .

(190) In the present embodiment, the difference in height between the glossy portions **2052** and the less-glossy portions **2051** can be obtained by using a white-light interferometer and measuring a height of the less-glossy portions **2051** with respect to the glossy portions **2052**, which are a base surface of the flat-surface portion **2030**. For example, in the present embodiment, the difference in height was evaluated as an average of values obtained by performing measurement at ten points of a portion of the molded product. The size of the portion was 1.0 $\times$ 1.4 mm, and the measurement was performed by using 3D optical profiler NewView7000 made by ZYGO Corporation and an objective lens with a magnification of 10 times.

(191) The difference in glossiness between the less-glossy portions **2051** and the glossy portions **2052** may have any value as long as an observer can visually identify the difference. Preferably, the difference in glossiness is ten or more. Note that glossiness values in this description are measured by using a glossmeter, which is designed to measure a specular glossiness at a reflection angle of 60° under JIS Z 8741. For example, the measurement values on glossiness can be obtained by using a handy type gloss meter PG-1 made by NIPPON DENSHOKU INDUSTRIES CO. LTD. Specifically, the measurement values on glossiness can be obtained by setting the reflection angle at 60°, and pressing a photometer of the glossmeter against a glossy portion of the molded product.

(192) In addition, it is preferable that the fine concave-and-convex structure to achieve the less-glossy portion **2051** have a step that is 15 μm or less. The reason is that if the fine concave-and-convex structure is 15 μm or less, an observer cannot visually recognize the fine concave-and-convex structure as concave and convex portions and the mold can be released smoothly without damaging the resin component, with the help of contraction coefficient of the resin in the injection molding and elasticity of the resin, even when the fine concave-and-convex structure is formed in an undercut direction. Note that the present inventors confirmed through an experiment that if a resin component has a shape of a semicircular column with a width of 100 mm and the maximum step in a direction orthogonal to the mold releasing direction is 15 or less, the mold can be released smoothly from the resin component made of a resin such as ABS or HIPS (high impact polystyrene).

(193) Thus, in the present embodiment, the difference in height of the concave-and-convex pattern of the curved-surface portion **2031** (second portion) is not as large as that of the concave-and-convex pattern constituted by the convex portions **2041** and the flat portions **2042** of the flat-surface portion **2030** (first portion). However, the curved-surface portion **2031** has the surface pattern in which the glossy portions **2052** and the less-glossy portions **2051** are combined with each other by using the fine concave-and-convex structure whose maximum difference in height is 15 μm or less that allows the release of the mold. The surface pattern of the curved-surface portion **2031** is formed with a regular pattern that is the same as that constituted by the convex portions **2041** and the flat portions **2042** of the flat-surface portion **2030** (first portion).

(194) That is, in the present embodiment, on the boundary between the flat-surface portion **2030** and the curved-surface portion **2031**, the continuity of the glossiness pattern of the surface pattern formed on the decorative surface is at least kept. In the present embodiment, since the continuity of the glossiness pattern is kept on the boundary between the flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion) in this manner, it is effective that the gap in

visual impression on the boundary is inconspicuous (hardly recognized visually).

(195) If a checked pattern is used, the width of one flat portion **2042** or one convex portion **2041** (one glossy portion **2052** or one less-glossy portion **2051**) is preferably 1 mm or more. This is because if the width of one flat portion **2042** or one convex portion **2041** (one glossy portion **2052** or one less-glossy portion **2051**) is less than 1 mm, the glossy portions are difficult to visually recognize and the checked pattern is difficult for an observer (user) to visually identify.

(196) Note that the geometrical structure of the surface pattern formed on the outer surface **2011** of the resin component and including the areas of glossy and nonglossy (or concave and convex) portions is not limited to the checked pattern. That is, the geometrical structure of the surface pattern may be any pattern as long as the concave and convex portions and the glossiness allow an observer to visually recognize the surface pattern.

(197) FIGS. **4A** to **4C** illustrate examples of a geometrical structure of the regular surface pattern formed on the outer surface **2011** of the resin component and including the areas of glossy and nonglossy portions (or concave and convex portions). FIG. **4A** illustrates a polka-dotted pattern formed as a group of circles. FIG. **4B** illustrates a star-shaped pattern formed as a group of stars. FIG. **4C** illustrates a triangle (scale) pattern. Thus, if the surface pattern, in which an area of an identical glossy portion and an identical nonglossy portion (or an area of a concave portion and a convex portion) is repeatedly disposed under a specific rule, is used, the resin component can be easily manufactured advantageously. Note that since the surface patterns illustrated in FIGS. **4A** to **4C** are merely examples, the surface pattern in which concave and convex portions or glossy and nonglossy portions are alternately arranged may be appropriately changed in design by a person skilled in the art.

(198) In the present embodiment, the material of the resin component including the outer surface **2011** that constitutes a housing or a case of an electronic device may be a resin material such as ABS or HIPS (high impact polystyrene).

(199) Next, a method of manufacturing a resin component of the present embodiment will be described. For example, the resin component can be injection-molded by injecting resin from a gate into a cavity formed in the mold, and by filling the cavity with the resin (forming or molding process).

(200) FIG. **5** illustrates a configuration of a machining center that machines a mold used to mold the resin component of the present embodiment. A machining center **90** of FIG. **5** includes a machine body **91** and a control device **92**. The cavity may be formed by a plurality of pieces (cavity pieces) each of which forms one portion of the mold. Thus, if the cavity is formed by the cavity pieces, a transfer surface can be divided into pieces of the surface, and the pieces of the surface can be individually machined. Thus, even though a molded product has a complex shape, production cost for the mold can be reduced.

(201) The machine body **91** is used to manufacture the mold (cavity piece) **93** by cutting the mold **93**, which is an object to be machined. The machine body **91** includes a spindle **95**, an X stage **96**, a Y stage **97**, and a Z stage **98**. The spindle **95** is a spindle that supports a cutting tool **94**.

(202) As the cutting tool **94**, an end mill can be suitably used. The spindle **95** rotates the cutting tool **94** on a Z axis. The Z stage **98** supports the spindle **95**, and moves the cutting tool **94** in a Z-direction with respect to the mold **93**. Similarly, the X stage **96** moves the cutting tool **94** in an X-direction with respect to the mold **93**, and the Y stage **97** moves the cutting tool **94** in a Y-direction. With such a configuration, the machine body **91** moves an end of the cutting tool **94** in the X-, Y-, and Z-direction with respect to the mold **93**, while rotating the cutting tool **94**.

(203) The control device **92** is a computer including a CPU and a memory, and controls the machine body **91** depending on NC data **99**. The NC data **99** contains various instructions used in cutting process, such as the amount of movement in the X-direction, the amount of movement in the Y-direction, the amount of movement in the Z-direction, rotational speed of the spindle, feed speed in the X-direction, feed speed in the Y-direction, and feed speed in the Z-direction. The

control device **92** controls the machine body **91**, and thereby can move the cutting tool **94** with respect to the mold **93** while rotating the cutting tool **94**, so that a three-dimensional shape based on the NC data **99** can be formed in the mold **93** by cutting the mold **93**.

(204) FIGS. **6** and **24** illustrate manufacturing processes for a first molding surface and a second molding surface of the mold **93** used to mold the flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion) of the resin component of the present embodiment. FIG. **6A** illustrates a first mold-machining process, FIG. **6B** illustrates a second mold-machining process, and FIGS. **24A** and **24B** or **24C** illustrate a third mold-machining process. As illustrated in FIGS. **6** and **24**, a transfer pattern for the surface pattern of the above-described flat-surface portion **2030** (first portion) and the curved-surface portion **2031** (second portion) is formed, through machining, on the first molding surface and the second molding surface of the mold **93**.

(205) First, in the first mold-machining process illustrated in FIG. **6A**, a surface **101** of the mold **93** is roughly machined. A radius end mill **102** is used for the machining center of FIG. **5** as the cutting tool; and the surface of the mold **93** is cut, depending on the NC data **99**, by scanning the surface **101** with the radius end mill **102** while rotating the radius end mill **102**. Preferably, the surface **101** is cut in the first mold-machining process such that the flatness of the surface **101** is 10 μm or less, for eliminating a smoothing process to be performed in the second mold-machining process.

(206) In the second mold-machining process of FIG. **6B**, the surface **101** of the mold **93** is ground into a mirror surface by using a rotary grinder **103** and diamond paste. When the smooth mirror surface is transferred to the resin, the transferred portion forms the above-described glossy portion. Preferably, the surface **101** is ground in the second mold-machining process such that the flatness of the surface **101** is 5 μm or less, so that no difference in depth is produced in concave portions **104** when the concave portions **104** are machined in the third mold-machining process. Note that although FIGS. **6A** and **6B** illustrate machining for a flat surface, a curved surface can be similarly machined in accordance with predetermined curved-surface data designed by using CAD or the like.

(207) In the third mold-machining process, the surface **101** of the mold **93** is machined by using a ball end mill **106**. FIG. **24A** illustrates machining for forming a portion of the mold for the above-described flat-surface portion **2030** (FIG. **23B**), performed after the transfer pattern is transferred to the resin through injection molding. FIG. **24B** or **24C** illustrates machining for forming a portion of the mold for the above-described curved-surface portion **2031** (FIG. **23B**), performed after the transfer pattern is transferred to the resin through injection molding. Note that FIG. **24B** illustrates the machining for the curved-surface portion **2031** that is a convex surface as illustrated in FIG. **23B**, and FIG. **24C** illustrates the machining for the curved-surface portion **2031** that is a concave surface.

(208) As illustrated in FIG. **24A**, when a portion of the mold for the flat-surface portion **2030** is machined, the portion is cut and scanned, depending on the NC data **99**, while the ball end mill **106** is rotated, so that the concave portions **104** are formed. When the concave portions **104** are transferred to the resin component, the convex portions **2041** are formed in the resin component. The portion is further scanned by the ball end mill **106** for forming a plurality of concave portions **105** in the bottom surface of each concave portion **104**. With this operation, a fine concave-and-convex structure to form the less-glossy portion is formed in the bottom surface of the concave portion **104**.

(209) When the fine concave-and-convex structure is transferred to the resin component through injection molding, a fine concave-and-convex structure is formed on the convex portion **2041**. The fine concave-and-convex structure formed on the convex portion **41** serves as the less-glossy portion **2051**. In addition, as illustrated in FIG. **24B** or FIG. **24C**, for forming a portion of the mold for the curved-surface portion **2031**, a plurality of concave portions **105** are formed in the portion of the surface **101** of the mold at positions corresponding to the less-glossy portions **2051**. As illustrated in FIG. **24B**, in the curved-surface portion **2031**, concave portions similar to the concave

portions **104** of FIG. **24A** are not formed. As illustrated in FIGS. **24A** to **24C**, a portion of the mold in which a plurality of concave portions **105** are formed correspond to a less-glossy portion **2051**, and a portion of the mold in which the concave portions **105** are not formed correspond to a glossy portion **2052**.

(210) Note that the material of the mold **93** machined as described above may be stainless steel. However, the material may be any other material for the machinability and durability in the injection molding.

(211) In the above description, the molding for the resin component through injection molding and the manufacturing process for the mold have been described. However, the manufacturing method is not limited to the above description. The molding for the above-described resin component including the flat-surface portion **2030** and the curved-surface portion **2031** may be performed using another appropriate method other than the above-described injection molding. Hereinafter, more specific examples of the present embodiment will be described. Note that an identical member, size, or direction is given an identical reference symbol, and detailed description thereof will be omitted.

Example 4

(212) FIGS. **25A** to **25C** are diagrams illustrating a resin component of Example 4. FIG. **25A** is a plan view illustrating a height distribution, FIG. **25B** is a plan view illustrating a glossiness distribution, and FIG. **25C** illustrates a cross-sectional view. As illustrated in FIG. **25B**, a checked concave-and-convex or glossiness pattern was formed on a plate-like resin component **2080** having a thickness of 1.6 mm. Note that although the height distribution of the curved-surface portion of FIG. **25A** is illustrated as 0 μm for convenience of illustration, the curved-surface portion has a pattern of a fine concave-and-convex structure with a height of 5 μm as can be seen in the cross-sectional view of FIG. **25C**. The resin component **2080** includes a flat-surface portion **2081** (first portion) and a curved-surface portion **2082** (second portion). The curved-surface portion **2082** is formed at an edge of the flat-surface portion **2081**, and inclined with respect to the flat-surface portion **2081**. The curvature radius of the curved-surface portion **2082** is 60 mm, and an angle (θ) of a tangential line of the curved surface with respect to the flat-surface portion **2081** is 45 degrees at the maximum. The pitch of the checked pattern is 7 mm, and a step in the normal direction between a convex portion **2083** and a concave portion **2084** adjacent to each other is 50 μm .

(213) In the present example, the concave-and-convex pattern having a large difference in height is formed only on the flat-surface portion **2081**, and is not formed on the curved-surface portion **2082**. The glossiness pattern is constituted by the less-glossy portions **2085** and the glossy portions **2086**, and the less-glossy portions **2085** correspond to the convex portions **2083** and the glossy portions **2086** corresponds to the concave portions **2084**. Each of the nonglossy portions **84** has a fine concave-and-convex structure having a height of 5 μm and a 60° specular glossiness of 30. The 60° specular glossiness of the glossy portions **2086**, on which no fine concave-and-convex structure is formed, was set at 80. The glossiness pattern constituted by the less-glossy portions **2085** and the glossy portions **2086** was formed also on the curved-surface portion **2082**. The cross-section structure of the flat-surface portion **2081** and the curved-surface portion **2082** is illustrated in FIG. **25C**.

(214) The material of the mold for manufacturing the resin component of the present example was stainless steel. First, the radius end mill was fixed to the machining center of FIG. **5** and the mold was roughly machined, and then the surface of the mold was ground into a mirror surface by using the rotary grinder and diamond paste. Then, an inverted shape of a checked pattern constituted by the convex portions **2083**, the concave portions **2084**, the less-glossy portions **2085**, and the glossy portions **2086** was formed on the mold by using the ball end mill.

(215) After that, injection molding was performed by using the mold, for forming the resin component **2080**. The resin material used was a black HIPS, and the resin component **2080** was able to be released from the mold, without being damaged.

(216) Then, the outer surface of the resin component was visually observed by a person with the normal eyesight, for evaluating a gap on the boundary between the flat-surface portion **2081** and the curved-surface portion **2082**. As a result, although the gap caused by the presence and absence of the concave and convex portions was perceived depending on an angle at which the gap was viewed, it was confirmed that the gap is inconspicuous because the glossiness pattern is kept. In particular, it was confirmed that a visible gap for the boundary is significantly suppressed compared to a conventional resin component in which no glossiness pattern is formed in the curved-surface portion **2082**.

Example 5

(217) FIGS. **26A** to **26C** are diagrams illustrating a resin component of Example 5. FIG. **26A** is a plan view illustrating a height distribution, FIG. **26B** is a plan view illustrating a glossiness distribution, and FIG. **26C** illustrates a cross-sectional view. The pitch and the step of concave and convex portions of the checked pattern are the same as those of Example 4. Example 5 differs from Example 4 in that the concave and convex portions are formed also in the curved-surface portion **2082**. The height of the convex portions **2083** in the normal direction is monotonously decreased as an angle (θ) between the tangential direction of the curved-surface portion **2082** (second portion) of the present example and the flat-surface portion **2081** (first portion) increases. That is, the height is monotonously decreased as the difference in angle between the curved-surface portion and the flat-surface portion increases.

(218) That is, in this structure, the maximum difference in height in the normal direction between adjacent areas of the surface pattern of the curved-surface portion **2082** (second portion) is decreased as the angle between the tangential direction of the curved-surface portion **2082** (second portion) and the flat-surface portion **2081** (first portion) increases.

(219) Specifically, the height of the convex portions **2083** was decreased by 5 μm as the curved-surface portion **2082** extends from a point between the flat-surface portion **2081** and the curved-surface portion **2082**, outward (rightward in FIG. **26**) more by 7 mm (1 pitch). In addition, the curved-surface portion **2082** was formed such that the height of a convex portion **2083** becomes 10 μm when the curved-surface portion **2082** reaches a right edge at which the angle between the curved-surface portion **2082** and the flat-surface portion **2081** is 45 degrees.

(220) The glossiness pattern was formed, as in Example 4, such that the less-glossy portions **2085** correspond to the convex portions **2083** and the glossy portions **2086** correspond to the concave portions **2084**. The glossiness value of the less-glossy portions **2085** was set at **2030**, and the glossiness value of the glossy portions was set at **2080**. The glossiness pattern constituted by the less-glossy portions **2085** and the glossy portions **2086** was formed across the whole of both the flat-surface portion **2081** and the curved-surface portion **2082**. The cross-section structure of the flat-surface portion **2081** and the curved-surface portion **2082** is illustrated in FIG. **26C**.

(221) The material of the mold for manufacturing the resin component of the present example was stainless steel. First, the radius end mill was fixed to the machining center **90** of FIG. **5** and the mold was roughly machined, and then the surface of the mold was ground into a mirror surface by using the rotary grinder and diamond paste. Then, an inverted shape of a checked pattern constituted by the convex portions **2083**, the concave portions **2084**, the less-glossy portions **2085**, and the glossy portions **2086** was formed on the mold by using the ball end mill.

(222) After that, the resin component **2080** was produced by using the manufactured mold and casting the resin material in injection molding. In this operation, the resin material used was a black HIPS. The resin component **2080** was not damaged, and was able to be released from the mold smoothly.

(223) Then, the outer surface of the resin component was visually observed by a person with the normal eyesight, for evaluating a gap on the boundary between the flat-surface portion **2081** and the curved-surface portion **2082**. As a result, it was confirmed that the gap on the boundary is reduced (effect in Example 4) because the glossiness pattern is kept in the curved-surface portion

2082, and that the visible gap is more inconspicuous because the concave and convex portions change step by step.

Other Examples

(224) In the above-described embodiments and examples, the less-glossy portions correspond to the convex portions, and the glossy portions correspond to the concave portions. However, the relationship between the glossiness and the concave or convex portions is not limited to this. The decorative surface that expresses a certain design may have a surface pattern in which the less-glossy portions correspond to the concave portions and the glossy portions correspond to the convex portions. For example, the fine concave-and-convex structure may be formed on the concave portions of the resin component.

(225) In addition, although the glossiness pattern is equal to the concave-and-convex pattern in the above-described embodiments and examples, the glossiness pattern may not necessarily be equal to the concave-and-convex pattern. For example, the present invention can also be applied for a pattern having different spatial frequencies. In this case, if the spatial frequency of the glossiness pattern is higher than the spatial frequency of the concave-and-convex pattern, the visible gap of the boundary can be more reduced. This is because patterns with a high frequency attracts people more than patterns with a low frequency.

(226) In addition, although the height of the convex portions **2083** is changed linearly in steps of 5 μm in the above-described Example 5, the height may be set in accordance with the difference in angle between the flat-surface portion **2081** and the curved-surface portion **2082**. For example, if the mold releasing direction is orthogonal to the flat-surface portion **2081**, a difference DU in height between a convex portion and a concave portion formed in a direction orthogonal to a mold releasing direction that causes an undercut can be expressed by using the following equation (3).

$$D.\text{sub}.U=(D+D.\text{sub}.M)\sin(\theta) \quad (3)$$

(227) In the equation (3), D denotes a height of the convex portions **2083**, DM denotes a height of the fine concave-and-convex structure that forms the less-glossy portion **2085** on the convex portions **2083**, and θ is an angle between a base surface on which a convex portion **2083** is formed and the flat-surface portion **2081**. The height D of each convex portion of the curved-surface portion **2082** may be set such that DU is equal to or smaller than a height that allows the mold to be released.

(228) In addition, although the mold for the resin component of the present invention is formed through the cutting process in the above-described embodiments and examples, the method of machining the mold is not limited to this. For example, the mold may be manufactured by using another method, such as a method using a laser beam machine.

(229) The present invention can be suitably applied for a resin component whose outer surface includes an area in which a process such as lettering is performed, the resin component on which the process such as lettering has been performed, an electronic device in which the resin component is used, and a method of manufacturing the resin component. For example, a logo or the like can be given, through a process, to an outer surface of a product on which a design pattern having a difference in height (concave and convex portions) is formed, without significantly deteriorating the quality of external appearance in design. In addition, an inclined surface or a curved surface can be formed without significantly deteriorating the quality of external appearance in design.

Other Embodiments

(230) While the present invention has been described with reference to exemplary embodiments, it is to be understood that the invention is not limited to the disclosed exemplary embodiments. The scope of the following claims is to be accorded the broadest interpretation so as to encompass all such modifications and equivalent structures and functions.

Claims

1. A product comprising: a first region; and a second region located at a different position from the first region, wherein the first region includes a plurality of first concave-and-convex structures having a first optical property and a plurality of first flat areas having a second optical property, and the plurality of first concave-and-convex structures and the plurality of first flat areas are alternately arranged, wherein the second region includes a plurality of convex portions and a plurality of second flat areas having the second optical property, and a plurality of second concave-and-convex structures having the first optical property are arranged on upper surfaces of the plurality of convex portions, and the plurality of convex portions and the plurality of second flat areas are alternately arranged, and wherein a glossiness value of the first optical property is lower than a glossiness value of the second optical property, and a height of areas in which the plurality of first concave-and-convex structures are arranged is lower than a height of the upper surfaces of the plurality of convex portions.
2. The product according to claim 1, wherein the plurality of first concave-and-convex structures have a different surface roughness than the plurality of first flat areas.
3. The product according to claim 1, wherein a distance between a first concave-and-convex structure and a plane on which the plurality of first flat areas are arranged is equal to or smaller than 15 μm .
4. The product according to claim 1, wherein a distance between a second concave-and-convex structure and a plane on which the plurality of second flat areas are arranged is 15 μm to 500 μm .
5. The product according to claim 1, wherein a distance between a second concave-and-convex structure and a plane on which the plurality of second flat areas are arranged decreases as the second concave-and-convex structure is located closer to the first region.
6. The product according to claim 1, wherein a first concave-and-convex structure is arranged on upper surfaces of each of a plurality of first convex portions provided in the first region, and a second concave-and-convex structure is arranged on upper surfaces of each of plurality of convex portions provided in the second region.
7. The product according to claim 1, wherein the glossiness value changes linearly in a direction from the second region toward the first region.
8. The product according to claim 1, further comprising a third optical property area formed in the first region.
9. The product according to claim 1, wherein at least one of characters, numerals, and a figure is given to the first region.
10. The product according to claim 1, wherein the first region is located on a curved surface.
11. The product according to claim 1, wherein a distance between a second concave-and-convex structure and a plane on which the plurality of second flat areas are arranged changes such that a glossiness value of an outer surface changes linearly in an arrangement direction of the plurality of second concave-and-convex structures.
12. The product according to claim 11, wherein the plurality of second concave-and-convex structures have an identical length in the arrangement direction of the plurality of second concave-and-convex structures.
13. The product according to claim 11, wherein a pitch of each second concave-and-convex structure is less than 1 mm.
14. The product according to claim 11, wherein the glossiness value is a 60° specular glossiness.
15. The product according to claim 11, wherein the plurality of first concave-and-convex structures contain an area to which at least one of characters, numerals, and a figure is given.
16. An electronic device comprising the product according to claim 1 and an electronic component.
17. The product according to claim 1, wherein glossiness of the plurality of first concave-and-convex structures is lower than glossiness of the plurality of first flat areas, and glossiness of the

plurality of second concave-and-convex structures is lower than glossiness of the plurality of second flat areas.
