

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12413051
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Ishida; Misaki et al.

Surface emitting laser module, optical device, and surface emitting laser substrate

Abstract

A surface emitting laser module includes a base substrate, a surface emitting laser substrate mounted on the base substrate, the surface emitting laser substrate including a surface emitting laser element, and the surface emitting laser substrate having a first face facing the base substrate and a second face facing away from the base substrate, and an optical member facing the second face and including an optical element configured to receive light emitted from the second face of the surface emitting laser element. The surface emitting laser element includes a first semiconductor layer, a second semiconductor layer, a first electrode provided on the first face and connected to the first semiconductor layer, and a second electrode provided on the first face and connected to the second semiconductor layer. The base substrate includes a third electrode connected to the first electrode and a fourth electrode connected to the second electrode.

Inventors:	Ishida; Misaki (Kanagawa, JP), Jikutani; Naoto (Miyagi, JP), Izumiya; Kazuma (Miyagi, JP)
Applicant:	RICOH COMPANY, LTD. (Tokyo, JP)
Family ID:	69630576
Assignee:	RICOH COMPANY, LTD. (Tokyo, JP)
Appl. No.:	17/419826
Filed (or PCT Filed):	January 28, 2020
PCT No.:	PCT/JP2020/003011
PCT Pub. No.:	WO2020/158744
PCT Pub. Date:	August 06, 2020

Prior Publication Data

Foreign Application Priority Data

JP 2019-016353 Jan. 31, 2019

Publication Classification**Int. Cl.:** H01S5/00 (20060101); H01S5/02253 (20210101); H01S5/0234 (20210101); H01S5/0237 (20210101); H01S5/042 (20060101); H01S5/183 (20060101); H01S5/42 (20060101); G01S7/481 (20060101)**U.S. Cl.:****CPC** H01S5/423 (20130101); H01S5/005 (20130101); H01S5/02253 (20210101); H01S5/0234 (20210101); H01S5/0237 (20210101); H01S5/04256 (20190801); H01S5/18305 (20130101); G01S7/4814 (20130101)**Field of Classification Search****USPC:** 356/4.01**References Cited****U.S. PATENT DOCUMENTS**

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6724794	12/2003	Dudoff	372/12	H01L 33/0095
6956244	12/2004	Dudoff	257/E25.032	H01L 33/385
6959025	12/2004	Jikutani et al.	N/A	N/A
7180100	12/2006	Takahashi et al.	N/A	N/A
7324717	12/2007	Chua et al.	N/A	N/A
7700955	12/2009	Kuwata et al.	N/A	N/A
7777173	12/2009	Price	250/221	G01S 7/481
9859681	12/2017	Adachi et al.	N/A	N/A
9966730	12/2017	Adachi et al.	N/A	N/A
10244181	12/2018	Warren	N/A	H04N 23/56
2003/0013217	12/2002	Dudoff et al.	N/A	N/A
2004/0200573	12/2003	Dudoff et al.	N/A	N/A
2005/0040413	12/2004	Takahashi	257/96	B82Y 20/00
2005/0100068	12/2004	Jikutani	372/96	B82Y 20/00
2007/0126010	12/2006	Chua	257/E31.127	H01L 31/02327
2007/0241933	12/2006	Price et al.	N/A	N/A
2008/0224167	12/2007	Kuwata	257/E33.062	H01L 27/15
2016/0043528	12/2015	Adachi et al.	N/A	N/A
2016/0164261	12/2015	Warren	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
H08-288590	12/1995	JP	N/A
2007-142425	12/2006	JP	N/A
2007-227676	12/2006	JP	N/A
2008-517279	12/2007	JP	N/A
2008-226948	12/2007	JP	N/A
2008-227404	12/2007	JP	N/A
2010-191123	12/2009	JP	N/A
2015-028658	12/2014	JP	N/A
2016-213412	12/2015	JP	N/A
2017-017296	12/2016	JP	N/A
2009/001461	12/2007	WO	N/A

OTHER PUBLICATIONS

Office Action issued on Aug. 2, 2022, in corresponding Japanese patent Application No. 2019-016353, 2 pages. cited by applicant

Office Action issued Jan. 17, 2023, in Korean Patent Application No. 10-2021-7020618, 11 pages. cited by applicant

Office Action issued Jul. 13, 2022, in Korean Patent Application No. 10-2021-7020618, 10 pages. cited by applicant

International Search Report and Written Opinion issued Apr. 21, 2020 in PCT/JP2020/003011 filed Jan. 28, 2020. cited by applicant

Primary Examiner: Hulka; James R

Attorney, Agent or Firm: XSENSUS LLP

Background/Summary

TECHNICAL FIELD

(1) The present invention relates to a surface emitting laser module, an optical device, and a surface emitting laser substrate.

BACKGROUND ART

(2) A vertical cavity surface emitting laser (VCSEL) is a semiconductor laser that oscillates laser light in a direction perpendicular to the substrate. The VCSEL has features such as a lower threshold current, a single longitudinal mode oscillation, and a two dimensional array arrangement. The VCSEL is sometimes used in combination with a microlens array.

(3) PTL 1 describes a device in which a surface formed with laser mesas (VCSEL elements) of a VCSEL device is oriented toward a microlens array, and the microlens array is mounted on this surface. In this photonic device, a plurality of electrode pads each of which is individually connected to a corresponding one of the VCSEL elements are provided on the surface formed with the VCSEL elements. These multiple electrode pads are provided at the outside of the part where the microlens array comes into contact with the VCSEL device, and are connected to the IC package by wire bonding.

(4) According to the device described in PTL 1, the microlens array can be integrated into a

VCSEL device.

SUMMARY OF INVENTION

Technical Problem

(5) However, even though there is a demand for reducing the sizes of surface emitting laser substrates such as VCSEL devices, the structure described in PTL 1 cannot sufficiently meet the demand for the reduction of the sizes.

(6) It is an object of the present invention to provide a surface emitting laser module, an optical device, and a surface emitting laser substrate of which the size can be further reduced.

Solution to Problem

(7) According to an aspect of the technique of the present disclosure, a surface emitting laser module includes a base substrate, a surface emitting laser substrate mounted on the base substrate, the surface emitting laser substrate including a surface emitting laser element, and the surface emitting laser substrate having a first face facing the base substrate and a second face facing away from the base substrate, and an optical member facing the second face and including an optical element configured to receive light emitted from the second face of the surface emitting laser element. The surface emitting laser element includes a first semiconductor layer of a first conductivity type, a second semiconductor layer of a second conductivity type, a first electrode provided on the first face and connected to the first semiconductor layer, and a second electrode provided on the first face and connected to the second semiconductor layer. The base substrate has a third face facing the first face of the surface emitting laser substrate, and includes a third electrode provided on the third face and connected to the first electrode and a fourth electrode provided on the third face and connected to the second electrode.

Advantageous Effects of Invention

(8) According to the technique of the present disclosure, the size of the surface emitting laser substrate can be further reduced.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) FIG. 1 is a top view illustrating a surface emitting laser module according to a first embodiment;

(2) FIG. 2 is a cross-sectional view (part 1) illustrating the surface emitting laser module according to the first embodiment;

(3) FIG. 3 is a cross-sectional view (part 2) illustrating the surface emitting laser module according to the first embodiment;

(4) FIG. 4 is a cross-sectional view illustrating a part of FIG. 2 in an enlarged manner;

(5) FIG. 5 is a cross-sectional view illustrating a part of FIG. 3 in an enlarged manner;

(6) FIG. 6 is a bottom view illustrating a VCSEL chip according to the first embodiment;

(7) FIG. 7 is a top view illustrating a VCSEL chip according to the first embodiment;

(8) FIG. 8 is a bottom view illustrating an MLA according to the first embodiment;

(9) FIG. 9 is a cross-sectional view illustrating the MLA according to the first embodiment;

(10) FIG. 10A is a cross-sectional view (part 1) illustrating a method for forming the VCSEL chip according to the first embodiment;

(11) FIG. 10B is a cross-sectional view (part 2) illustrating the method for forming the VCSEL chip according to the first embodiment;

(12) FIG. 10C is a cross-sectional view (part 3) illustrating the method for forming the VCSEL chip according to the first embodiment;

(13) FIG. 10D is a cross-sectional view (part 4) illustrating the method for forming the VCSEL chip according to the first embodiment;

- (14) FIG. 10E is a cross-sectional view (part 5) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (15) FIG. 10F is a cross-sectional view (part 6) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (16) FIG. 10G is a cross-sectional view (part 7) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (17) FIG. 11A is a cross-sectional view (part 8) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (18) FIG. 11B is a cross-sectional view (part 9) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (19) FIG. 11C is a cross-sectional view (part 10) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (20) FIG. 11D is a cross-sectional view (part 11) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (21) FIG. 11E is a cross-sectional view (part 12) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (22) FIG. 11F is a cross-sectional view (part 13) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (23) FIG. 11G is a cross-sectional view (part 14) illustrating the method for forming the VCSEL chip according to the first embodiment;
- (24) FIG. 12 is a cross-sectional view illustrating a surface emitting laser module according to a reference example;
- (25) FIG. 13 is a top view illustrating a VCSEL chip according to the reference example;
- (26) FIG. 14 is a bottom view illustrating a VCSEL chip according to a modification of the first embodiment;
- (27) FIG. 15 is a top view illustrating a surface emitting laser module according to a second embodiment;
- (28) FIG. 16 is a cross-sectional view illustrating a surface emitting laser module according to the second embodiment;
- (29) FIG. 17 is a cross-sectional view illustrating a portion of FIG. 16 in an enlarged manner;
- (30) FIG. 18 is a cross-sectional view illustrating a surface emitting laser module according to a modification of the second embodiment; and
- (31) FIG. 19 is a drawing illustrating a distance measuring device according to a third embodiment.

DESCRIPTION OF EMBODIMENTS

(32) Hereinafter, the embodiments of the present disclosure will be specifically described with reference to the accompanying drawings. In this specification and drawings, constituent elements having substantially the same functional configurations may be denoted with the same reference numerals and redundant description thereabout may be omitted. In the present disclosure, in explanations about arrangements of components, with regard to a substrate, a direction away from the substrate may be referred to as an upward direction. For example, a film formed to be in contact with a lower surface of the substrate may be referred to as a film formed on the lower surface of the substrate.

First Embodiment

(33) First, the first embodiment will be explained. The first embodiment relates to a surface emitting laser module. FIG. 1 is a top view illustrating the surface emitting laser module according to the first embodiment. FIG. 2 and FIG. 3 are cross-sectional views illustrating the surface emitting laser module according to the first embodiment. FIG. 2 corresponds to a cross-sectional view taken along line I-I of FIG. 1. FIG. 3 corresponds to a cross-sectional view taken along line II-II of FIG. 1. FIG. 4 is a cross-sectional view illustrating a part of FIG. 2 in an enlarged manner. FIG. 5 is a cross-sectional view illustrating a part of FIG. 3 in an enlarged manner. FIG. 6 is a

bottom view illustrating a vertical cavity surface emitting laser (VCSEL) chip according to the first embodiment. FIG. 7 is a top view illustrating the VCSEL chip according to the first embodiment. The cross section of the VCSEL chip in FIG. 4 corresponds to the cross section taken along line III-III of FIG. 6. The cross section of the VCSEL chip in FIG. 5 corresponds to the cross section taken along line IV-IV of FIG. 6. FIG. 8 is a bottom view illustrating a micro lens array (MLA) according to the first embodiment. FIG. 9 is a cross-sectional view illustrating the MLA according to the first embodiment.

(34) As illustrated in FIG. 1 to FIG. 5, the surface emitting laser module **100** according to the first embodiment includes a base substrate **120**, a VCSEL chip **140** that is mounted on the base substrate **120** and that includes VCSEL elements, and a MLA **160** including microlenses **162** which receive light exiting from the VCSEL elements. The VCSEL element is an example of a surface emitting laser element. The VCSEL chip **140** is an example of a surface emitting laser substrate. The microlens **162** is an example of an optical element. The MLA **160** is an example of an optical member. That is, the VCSEL chip **140** is an embodiment of a surface emitting laser substrate.

(35) In the following description, unless otherwise specified, a direction in which the VCSEL chip **140** is located with respect to the base substrate **120** is referred to as upward, and a direction in which the base substrate **120** is located with respect to the VCSEL chip **140** is referred to as downward. However, the surface emitting laser module **100** can be used upside down, and can be placed at any angle. Also, a top view refers to viewing a target object from a direction normal to an upper face **141b** of the VCSEL chip **140**. A planar shape refers to a shape of a target object viewed from the direction normal to the face **141b** of the VCSEL chip **140**.

(36) In each drawing, the direction normal to the face **141b** of the VCSEL chip **140** is defined as a direction Z. In the top view, a direction parallel to one side of the face **141b** of the VCSEL chip **140** is defined as a direction X. A direction perpendicular to the direction X and the direction Z is defined as a direction Y.

(37) <Structure of VCSEL Chip **140**>

(38) Here, the structure of the VCSEL chip **140** will be described. In the explanation about the structure of the VCSEL chip **140** and the explanation about the method for forming the VCSEL chip **140** explained later, a direction (direction $-Z$ in FIG. 2 to FIG. 5) in which the base substrate **120** is located with respect to the VCSEL chip **140** is defined as an upper side.

(39) As illustrated in FIG. 6, the planar shape of the VCSEL chip **140** is, for example, a quadrangle, and a light emitting element unit **158** of which the planar shape is a quadrangle is provided at substantially the center of a face **141a** facing the base substrate **120**. The face **141a** is an example of a first face. The face **141b** is an example of a second face. In the light emitting element unit **158**, a plurality of VCSEL elements **159** are arranged in a manner of an array. For example, a total of 36 VCSEL elements **159** are arranged in 6 by 6 grids in the direction X and the direction Y. Each of the VCSEL elements **159** is monolithically fabricated on a substrate **141** such as an n-GaAs substrate, and all of the VCSEL elements **159** have the same film configuration. Each of the VCSEL elements **159** is, for example, a surface emitting laser with an oscillation wavelength of 940 nm.

(40) The first electrodes **157** are provided at the four corners of the face **141a** at the outside of the light emitting element unit **158**. The face **141a** is provided with 36 second electrodes **155** in total with 9 second electrodes **155** being arranged on each side of the light emitting element unit **158**. The four first electrodes **157** are connected commonly to the n-side electrodes of the 36 VCSEL elements **159**. Each of the 36 second electrodes **155** is individually connected to the p-side electrode of a corresponding one of the 36 VCSEL elements **159** through an interconnect **155a**. The four corners of the face **141a** mean the vicinities of the corners of the face **141a**, and the first electrodes **157** are not necessarily required to be in contact with the edge of the face **141a**.

(41) As illustrated in FIG. 7, the fixing patterns **181** are formed as adhesion fixing regions at the four corners of a face **141b** of the VCSEL chip **140** facing the MLA **160**. For example, the fixing

pattern **181** has a pattern of a stacked film in which titanium (Ti), platinum (Pt), and gold (Au) are stacked in this order from the face **141b**. The adhesive fixing region is an example of a bonding region.

(42) For example, the VCSEL element **159** includes, on a substrate **141** such as an n-GaAs substrate and the like, a contact layer **142**, a semiconductor multilayer reflector **143**, a spacer layer **144**, an active layer **145**, a spacer layer **146**, a semiconductor multilayer reflector **147**, a selectively oxidized layer **151**, and a contact layer **148**. The selectively oxidized layer **151** includes an oxidized area **151a** and a non-oxidized area **151b**.

(43) The contact layer **142** is formed on the substrate **141**. The contact layer **142** is, for example, an n-GaAs layer.

(44) The semiconductor multilayer reflector **143** is formed on the contact layer **142**. The semiconductor multilayer reflector **143** includes, for example, low refractive index layers made of n-Al.sub.0.9Ga.sub.0.1As and high refractive index layers made of n-Al.sub.0.2Ga.sub.0.8As. For example, the semiconductor multilayer reflector **143** includes 30 pairs of the low refractive index layers and the high refractive index layers.

(45) Between the refractive index layers of the semiconductor multilayer reflector **143**, there is provided a composition gradient layer having a thickness of, for example, 20 nm, in which the composition is gradually changed from one composition to another composition in order to reduce electrical resistance. Where the oscillation wavelength is denoted as λ , the film thickness of each of the refractive index layers, including $\frac{1}{2}$ of the adjacent composition gradient layer, is configured to have an optical thickness of $\lambda/4$. It should be noted that, where the optical thickness is $\lambda/4$, the actual thickness D of the layer is $\lambda/4n$ (where n denotes the refractive index of the medium of the layer).

(46) The spacer layer **144** is formed on the semiconductor multilayer reflector **143**. The spacer layer **144** is, for example, a non-doped AlGaInP layer.

(47) The active layer **145** is formed on the spacer layer **144**. The active layer **145** is an active layer having a triple quantum well structure having, for example, three quantum well layers and four barrier layers. For example, the quantum well layers are InGaAs layers and the barrier layers are AlGaAs layers.

(48) The spacer layer **146** is formed on the active layer **145**. The spacer layer **146** is, for example, a non-doped AlGaInP layer.

(49) A portion including the spacer layer **144**, the active layer **145**, and the spacer layer **146** is also referred to as a resonator structure (resonator area), and is configured to have an optical thickness of 1 wavelength (λ), including $\frac{1}{2}$ of the adjacent composition position gradient layer. The active layer **145** is provided at the center of the resonator structure, which is a position corresponding to the antinode in the standing wave distribution of the electric field, so that a high stimulated emission probability can be obtained.

(50) The semiconductor multilayer reflector **147** is formed on the spacer layer **146**. For example, the semiconductor multilayer reflector **147** includes low refractive index layers made of p-Al.sub.0.9Ga.sub.0.1As and high refractive index layers made of p-Al.sub.0.2Ga.sub.0.8As. For example, the semiconductor multilayer reflector **147** includes 20 pairs of the low refractive index layers and the high refractive index layers.

(51) Between the refractive index layers of the semiconductor multilayer reflector **147**, there is provided a composition gradient layer having a thickness of, for example, 20 nm, in which the composition is gradually changed from one composition to another composition in order to reduce electrical resistance. Where the oscillation wavelength is denoted as λ , the film thickness of each of the refractive index layers, including $\frac{1}{2}$ of the adjacent composition gradient layer, is configured to have an optical thickness of $\lambda/4$.

(52) In the semiconductor multilayer reflector **147**, a selectively oxidized layer **151** made of, for example, p-AlAs is inserted with a thickness of, for example, 30 nm. The insertion position of the

selectively oxidized layer **151** can be, for example, within the second pair, counted from the spacer layer **146**, of the high refractive index layer and the low refractive index layer. It should be noted that the selectively oxidized layer **151** may include layers such as a composition gradient layer and an intermediate layer disposed above and below the selectively oxidized layer **151**, and here, the layers that are actually oxidized are collectively referred to as a selectively oxidized layer.

(53) The contact layer **148** is formed on the semiconductor multilayer reflector **147**. The contact layer **148** is, for example, a p-GaAs layer.

(54) Mesas **150a** corresponding to the VCSEL elements **159** are formed in the light emitting element unit **158** by removing parts of the contact layer **148**, the semi-conductor multilayer reflector **147**, the spacer layer **146**, and the active layer **145** by etching. Further, mesas **150b** are formed at positions corresponding to the second electrodes **155** at the outside of the light emitting element unit **158**. The spacer layer **144** and the semiconductor multilayer reflector **143** are divided between the adjacent mesa **150a**, and a groove **152** reaching the contact layer **142** is formed.

(55) An insulating layer **153** covering the mesas **150a** and **150b** is formed. For example, SiN, SiON, SiO.sub.2 or the like can be used as a material of the insulating layer **153**. In the insulating layer **153**, an opening portion **154** exposing a part of the contact layer **148** of each of the mesas **150a** is formed. The opening portion **154** is formed at a position overlapping the non-oxidized area **151b** in the top view.

(56) A p-side electrode **155b** electrically connected to the contact layer **148** through the opening portion **154** is formed on the insulating layer **153** independently for each of the mesas **150a**. Each of the p-side electrodes **155b** is individually connected to a corresponding one of the second electrodes **155** via an interconnect **155a**. For example, the p-side electrode **155b**, the interconnect **155a**, and the second electrode **155** are configured as a stacked film in which Ti, Pt, and Au are stacked in order from the side of the insulating layer **153**.

(57) For the mesa **150b**, an opening portion is not formed in the insulating layer **153**, and the contact layer **148** in the mesa **150b** is electrically insulated from the second electrode **155**. Therefore, no current flows in the mesa **150b**.

(58) Opening portions **156** are formed at the four corners of the insulating layer **153** at the outside of the light emitting element unit **158** so as to expose parts of the contact layer **142**. The first electrodes **157** are formed to be electrically connected to the contact layer **142** through the opening portions **156**. The first electrodes **157** also serve as the n-side electrode of each of the VCSEL chips **140**. For example, the first electrode **157** has a stacked film in which gold germanium alloy (AuGe), nickel (Ni), and gold (Au) are stacked in order from the side of the contact layer **142**.

(59) On a face **121a** of the base substrate **120** facing the face **141a**, third electrodes **122** bonded to the first electrodes **157** and fourth electrodes **123** bonded to the second electrodes **155** are formed on the substrate **121**. The face **121a** is an example of a third face. For example, the number of the third electrodes **122** is 4, and the number of the fourth electrodes **123** is 36. The VCSEL chip **140** is flip-chip mounted on the base substrate **120**. The third electrodes **122** and the fourth electrodes **123** are, for example, Au plating films having a thickness of 2 μm .

(60) <Structure of MLA **160**>

(61) Hereinafter, the MLA **160** will be explained.

(62) The MLA **160** has a transparent substrate **161** made of, for example, quartz glass. A lens area **166** is provided at substantially the central portion of the face of the MLA **160** facing the VCSEL chip **140**. For example, in the lens area **166**, a total of 36 microlenses **162** are arranged in a manner of an array at positions corresponding to the respective VCSEL elements **159**. Each of the microlenses **162** is designed to perform a desired beam shaping for the radiation pattern of the VCSEL element **159**. For example, the lens diameter is 45 μm and the focal length is 70 μm .

(63) Anti-reflection films **168** are formed on both sides of the MLA **160**. The anti-reflection film **168** is, for example, a stacked film in which HfO.sub.2 and SiO.sub.2 are stacked in order from the side of the transparent substrate **161**, and is designed to have a transmittance of 99% or more for

light in a predetermined wavelength region including 940 nm, i.e., the oscillation wavelength of VCSEL element **159**.

(64) Leg portions **163** for defining the distance from the VCSEL chip **140** are formed to extend from the transparent substrate **161** at the four corners of the face of the MLA **160** facing the VCSEL chip **140**. On the bottom faces of the leg portions **163**, fixing patterns **164** are formed as adhesion fixing regions. For example, the fixing pattern **164** has a pattern of a stacked film in which Ti, Pt, and Au are stacked by vapor deposition in order from the side of the leg portion **163**.

(65) Each of the fixing patterns **164** is not necessarily required to be formed on the entire bottom surface of the leg portion **163** as long as the fixing pattern **164** is formed at a position facing the corresponding fixing pattern **181**. The planar shape of the fixing pattern **164** is preferably equal to the planar shape of the fixing pattern **181**.

(66) As illustrated in FIG. 4 and the like, the fixing pattern **164** and the fixing pattern **181** are bonded to each other by an adhesive agent **182** such as low-temperature solder. The adhesive agent **182** is an example of a bonding member.

(67) In the surface emitting laser module **100** configured as described above, the VCSEL elements **159** emit light from the face **141b** of the VCSEL chip **140**, and the emitted light enters the microlens **162** to be made into parallel light.

(68) <Method for Forming VCSEL Chip **140**>

(69) Hereinafter, a method for forming the VCSEL chip **140** will be described. FIG. 10A to FIG. 10G are cross-sectional views illustrating the method forming the VCSEL chip **140**. FIG. 10A to FIG. 10G illustrate changes in the cross section taken along line III-III of FIG. 6. FIG. 11A to FIG. 11G illustrate changes in the cross section taken along line IV-IV of FIG. 6.

(70) First, as illustrated in FIG. 10A, the contact layer **142**, the semiconductor multilayer reflector **143**, the spacer layer **144**, the active layer **145**, the spacer layer **146**, the semiconductor multilayer reflector **147**, and the contact layer **148** are grown in order on the substrate **141**. For example, the selectively oxidized layer **151** (not illustrated) made of p-AlAs is included in the semiconductor multilayer reflector **147**. A semiconductor stacked structure including the contact layer **142**, the semiconductor multilayer reflector **143**, the spacer layer **144**, the active layer **145**, the spacer layer **146**, the semiconductor multilayer reflector **147**, and the contact layer **148** can be prepared, for example, by crystal growth according to a metal organic chemical vapor deposition (MOCVD) method or a molecular beam epitaxy (MBE) method. Here, an example using the MOCVD method will be explained. For example, trimethylaluminum (TMA), trimethylgallium (TMG), trimethylindium (TMI), and the like are used as materials of Group III, and phosphine (PH.sub.3), and arsine (AsH.sub.3) are used as materials of Group V. As an example, carbon tetrabromide (CBr.sub.4) is used as the material of the p-type dopant, and hydrogen selenide (H.sub.2Se) is used as the material of the n-type dopant. For example, the substrate **141** is an n-GaAs substrate whose surface is a mirror-polished surface.

(71) Next, a resist pattern (not illustrated) is formed according to the desired planar shape of the mesas **150a** and **150b** on the contact layer **142** by using photolithography. Then, for example, parts of the semiconductor stacked structure that are not covered with the resist pattern are etched by, for example, an electron cyclotron resonance (ECR) etching method using Cl.sub.2 gas. As a result, as illustrated in FIG. 10B and FIG. 11A, the mesas **150a** and **150b** are formed. At this time, the mesas **150a** and **150b** are formed so as to expose at least the selectively oxidized layer **151** (not illustrated). After etching, the resist pattern is removed. The etching bottom surface can be, for example, the upper surface of the spacer layer **144**.

(72) Next, as illustrated in FIG. 10C and FIG. 11B, in steam, thermal treatment (oxidation treatment) is applied to the semiconductor stacked structure, as an oxidation target, in which the mesas **150a** and **150b** are formed. As a result, Al (aluminum) in the selectively oxidized layer **151** is selectively oxidized from the outer periphery of the mesas **150a** and **150b**. Then, the non-oxidized area **151b** that is not oxidized and that is surrounded by the oxidized area **151a** of Al is

left in the center of each of the mesas **150a** and **150b**. As a result, an oxide-confined structure is formed that restricts the drive current path of the light emitting unit only to the central part of the mesa **150a**. The non-oxidized area **151b** is a current passage area (current injection area).

(73) Next, as illustrated in FIG. **10D** and FIG. **11C**, using photolithography, a resist pattern (not illustrated) is formed on the contact layer **142** and the spacer layer **144** according to the planar shape of the grooves **152**. This resist pattern is formed so as to expose the areas where the first electrodes **157** are to be formed. Then, parts of the semiconductor stacked structure that are not covered with the resist pattern are etched by, for example, the ECR etching method using Cl.sub.2 gas, whereby the grooves **152** reaching the contact layer **142** are formed. At this time, the contact layer **142** is exposed in the areas where the first electrodes **157** are to be formed. After the etching, the resist pattern is removed.

(74) Next, as illustrated in FIG. **10E** and FIG. **11D**, for example, using the plasma CVD method, the optically transparent insulating layer **153** is formed so as to continuously cover the upper faces and side faces of the mesas **150a** and **150b**, the upper faces of the spacer layer **144**, and the inner walls (the bottom and side faces of the grooves **152**). Examples of materials of the insulating layer **153** include SiN, SiON, SiO.sub.2, and the like.

(75) Next, as illustrated in FIG. **10F**, by using photolithography, the insulating layer **153** formed on a part of the upper face of the mesa **150a** (excluding the outer peripheral part of the upper face of the contact layer **148**) is removed to make a window, whereby an opening portion **154** (contact area) is formed.

(76) Next, as illustrated in FIG. **10G** and FIG. **11E**, the p-side electrodes **155b**, the inter-connects **155a**, and the second electrodes **155** are formed by forming a resist pattern with photolithography, forming a metal film, and performing lift off. In forming the metal film, for example, Ti, Pt, and Au are stacked in order by vapor deposition on the insulating layer **153** and the contact layer **148** exposed through the opening portions **154**.

(77) Next, as illustrated in FIG. **11F**, by using photolithography, in each of the areas where the first electrodes **157** are to be formed, a part of the insulating layer **153** is removed to make a window, whereby an opening portion **156** (contact area) is formed.

(78) Next, as illustrated in FIG. **11G**, the first electrodes **157** serving as n-side electrodes are formed by forming a resist pattern with photolithography, forming a metal film, and performing lift off. In forming the metal film, for example, AuGe, Ni, and Au are stacked in order by vapor deposition on the contact layer **142** exposed through the opening portions **156**.

(79) As described above, the VCSEL chip **140** can be formed.

(80) <Method for Manufacturing Surface Emitting Laser Module **100**>

(81) Next, a method for manufacturing the surface emitting laser module **100** using the base substrate **120**, the VCSEL chip **140**, and the MLA **160** will be explained.

(82) In this method, first, the VCSEL chip **140** is flip-chip mounted on the base substrate **120**. As described above, the third electrodes **122** bonded to the first electrodes **157** and the fourth electrodes **123** bonded to the second electrode **155** are formed on the base substrate **120**. The VCSEL chip **140** is placed above the base substrate **120** so that the first electrodes **157** and the third electrodes **122** face each other with solders sandwiched therebetween, and the second electrodes **155** and the fourth electrodes **123** face each other with solders sandwiched therebetween, and the solders are melted and solidified through heating and cooling. As described above, the flip-chip bonding can be performed. Examples of usable solders include lead-free solder balls.

(83) Next, the MLA **160** is bonded onto the VCSEL chip **140** by, for example, a self-alignment method. That is, the relative positions of the VCSEL chip **140** and the MLA **160** are adjusted so that the fixing patterns **164** and the fixing patterns **181** almost overlap in the top view, and low temperature solders are disposed as the adhesive agents **182** between the fixing patterns **164** and the fixing patterns **181**. For example, examples of usable low temperature solders include solders with a melting point of about 140 degrees Celsius. Next, the MLA **160** bonded onto the VCSEL

chip **140** is heated in a nitrogen atmosphere to melt the low-temperature solder. The molten low-temperature solder spreads between the fixing patterns **181** of the VCSEL chip **140** and the fixing patterns **164** of the MLA **160**. At this time, a self-alignment occurs due to the restoring force of the molten low-temperature solder, and the MLA **160** can be aligned with the VCSEL chip **140** with high accuracy. In addition, the accuracy in the height direction can be ensured by applying same amounts of low-temperature solders to combinations at the four locations of the fixing patterns **181** and the fixing patterns **164**. For example, the amounts of low-temperature solders are adjusted so that the distance between the VCSEL chip **140** and the MLA **160** is 100 μm . Thereafter, through the cooling process, the bonding of the MLA **160** is completed. The bonding method according to the self-alignment method is described in, for example, Japanese Unexamined Patent Application Publication No. 2016-40822.

(84) Here, the effect of the present embodiment will be explained in comparison with a reference example. FIG. **12** is a cross-sectional view illustrating a surface emitting laser module according to the reference example. FIG. **13** is a top view illustrating a VCSEL chip according to the reference example.

(85) The surface emitting laser module **900** according to the reference example includes a base substrate **920**, a VCSEL chip **940** that is mounted on the base substrate **920** and that includes VCSEL elements, and an MLA **160**.

(86) The planar shape of the VCSEL chip **940** is a quadrangle, and a light emitting element unit **958** of which the planar shape is a quadrangle is provided at substantially the central portion of the face **941b** facing the MLA **960**. In the light emitting element unit **958**, a total of 36 mesas **950a** corresponding to the VCSEL elements are arranged in 6 by 6 grids in the direction X and the direction Y. Fixing patterns **981** are formed as adhesion fixing regions at the four corners of the face **941b** at the outside of the light emitting element unit **958**. Non-metal areas **983** are provided around the fixing patterns **981**.

(87) On the face **941b**, a total of 36 second electrodes **955** are arranged such that 9 second electrodes **955** are arranged along each side of the light emitting element unit **958**. Each of the 36 second electrodes **955** is individually connected to a p-side electrode of a corresponding one of the VCSEL elements via an interconnect **955a**. The n-side electrodes of the 36 VCSEL elements are formed on a face **941a** at the side opposite to the face **941b** of the VCSEL chip **940**, and are commonly connected to the electrode **922** formed on the substrate **921** of the base substrate **920**. Furthermore, each of the 36 second electrodes **955** is individually connected via a bonding wire **959** to a corresponding one of 36 electrodes **923** formed on the substrate **921** of the base substrate **920**. The second electrodes **955** are arranged at the outside of the quadrangle constituted by the four fixing patterns **981** in the top view in order to secure the space for the bonding wires **959** and due to limitation of the area by the non-metal areas **983**.

(88) In a case where the planar shape and the size of area of the light emitting element unit **158** are the same as the planar shape and the size of area of the light emitting element unit **958**, the size of area of the VCSEL chip **140** according to the first embodiment is smaller than the size of area of the VCSEL chip **940** according to the reference example.

(89) For example, in the first embodiment, the face **141a** provided with the second electrodes **155** is different from the face **141b** provided with the fixing patterns **181**. Therefore, the fixing patterns **181** may overlap at least one of the first electrodes **157** and the second electrodes **155** in the top view as long as the fixing patterns **181** are out of the path of the light emitted from the VCSEL elements **159**.

(90) In the reference example, the second electrodes **955** and the fixing patterns **981** are provided on the same face **941b**. For this reason, the non-metal area **983** is provided around the fixing pattern **981** in order to secure an insulating property. For example, in a case where the diameter of the fixing pattern **981** is 400 μm , the outer diameter of the non-metal area **983** is 800 μm .

Accordingly, the VCSEL chip **940** requires a large area for the arrangement of the fixing patterns

981.

(91) Further, in order to avoid contact between the bonding wire **959** and the MLA **160**, the second electrodes **955** are disposed at the outside of the MLA **160** in the top view. For example, in a case where the distance from the base substrate **920** to the apex of the bonding wire **959** is 120 μm and the distance from the base substrate **920** to the lower end of the microlens **162** is 100 μm , the bonding wires **959** come into contact with the MLA **160** unless the second electrodes **955** are arranged at the outside of the MLA **160** in the top view. Therefore, the VCSEL chip **940** requires a large area for the arrangement of the second electrodes **955**.

(92) In a case where the distance from the base substrate **920** to the lower end of microlens **162** is more than 120 μm , the contact can be avoided, but in this case, it is necessary to increase the focal length of the microlens **162**. In order to increase the focal length, it is necessary to increase the lens diameter. The increase in the lens diameter leads to an increase in the pitch of the microlenses **162** and the VCSEL elements. Therefore, also in this case, the size of the VCSEL chip **940** increases.

(93) In contrast, the first embodiment does not have such a restriction. Therefore, according to the first embodiment, the size of the VCSEL chip **140** can be reduced. The reduction in the size of the VCSEL chip **140** leads to an increase in the number of VCSEL chips **140** that can be cut out from a wafer of any give size, which results in an effect of reduction in the cost of the VCSEL chips **140**.

(94) The planar shape of the light emitting element unit **158** is not required to be a quadrangle, but may be a circle as illustrated in illustrated in FIG. **14**. In this case, on the face **141b** facing the MLA **160**, the fixing patterns **181** may be provided at positions that do not overlap either the first electrodes **157** or the second electrodes **155** in the top view.

(95) Further, the arrangement of the VCSEL elements **159** in the light emitting element unit **158** is not required to be in a manner of an array, and for example, the VCSEL elements **159** may be arranged in a honeycomb arrangement.

Second Embodiment

(96) Next, the second embodiment will be explained. The second embodiment relates to a surface emitting laser module. FIG. **15** is a top view illustrating a surface emitting laser module according to the second embodiment. FIG. **16** is a cross-sectional view illustrating a surface emitting laser module according to the second embodiment. FIG. **16** corresponds to a cross-sectional view taken along line I-I of FIG. **15**. FIG. **17** is a cross-sectional view illustrating a portion of FIG. **16** in an enlarged manner.

(97) As illustrated in FIG. **15** to FIG. **17**, a surface emitting laser module **200** according to the second embodiment includes a base substrate **220**, a VCSEL chip **140** that is mounted on the base substrate **220** and that includes VCSEL elements, and a MLA **260** including microlenses **262** which receive light exiting from the VCSEL elements. The VCSEL element is an example of a surface emitting laser element. The VCSEL chip **140** is an example of a surface emitting laser substrate. The microlens **262** is an example of an optical element. The MLA **260** is an example of an optical member.

(98) In the present embodiment, the fixing patterns **181** are not formed on the face **141b** of the VCSEL chip **140**.

(99) On a face **221a** of the base substrate **220** facing the face **141a**, third electrodes **122** bonded to the first electrodes **157** and fourth electrodes **123** bonded to the second electrodes **155** are formed on the substrate **221**. For example, the number of the third electrodes **122** is 4, and the number of the fourth electrodes **123** is 36. The VCSEL chips **140** are flip-chip mounted on the base substrate **120**. The fixing patterns **281** are formed as adhesion fixing regions at the four corners of the substrate **221** at the outside of the VCSEL chip **140** in the top view. The fixing pattern **281** has a pattern of a stacked film in which Ti, Pt, and Au are stacked in order from the side of the substrate **221**.

(100) The MLA **260** has a transparent substrate **261** made of, for example, quartz glass. The transparent substrate **261** is formed to be wider than the VCSEL chip **140** in the top view, and is

wider than the transparent substrate **161** in the first embodiment. A lens area is provided at substantially the central portion of the face of the MLA **260** facing the VCSEL chip **140**. For example, a total of 36 microlenses **262** are arranged in a manner of an array at positions corresponding to the respective VCSEL elements **159** in the lens area. Each microlens **262** is designed to perform a desired beam shaping for the radiation pattern of the VCSEL element **159**. For example, the lens diameter is 45 μm and the focal length is 70 μm . Anti-reflection films are formed on both sides of the MLA **260**.

(101) Leg portions **163** for defining the distance from the base substrate **220** are formed to extend from the transparent substrate **261** at the four corners of the MLA **260** facing the VCSEL chip **140**. On the bottom faces of the leg portions **163**, fixing patterns **164** are formed as adhesion fixing regions.

(102) The fixing pattern **164** and the fixing pattern **281** are bonded to each other by an adhesive agent **282** such as a low-temperature solder. The MLA **260** is bonded to the base substrate **220** by, for example, a self-alignment method. The adhesive agent **282** is an example of a bonding member.

(103) In the first embodiment, regardless of the size of the first electrodes **157** and the second electrodes **155**, the VCSEL chip **140** includes areas for the fixing patterns **181**. Therefore, in a case where the first electrodes **157** and the second electrodes **155** are relatively small, the size of the VCSEL chip **140** is likely to be affected by the size of the fixing patterns **181**.

(104) In the second embodiment, the fixing patterns **281** are provided on the base substrate **220**. Therefore, the VCSEL chip **140** does not require an area for the fixing patterns. Therefore, the size of the VCSEL chip **140** is not affected by the size of the fixing patterns **181**, and when the first electrodes **157** and the second electrodes **155** are small, the size of the VCSEL chip **140** can be reduced accordingly.

(105) It should be noted that the fixing pattern **164** and the fixing pattern **281** are not required to be bonded by a single adhesive agent **282**, and for example, as illustrated in FIG. **18**, a spacer **385** may be provided between the fixing pattern **164** and the fixing pattern **281**. In this modification, the spacer **385** is fixed to the fixing pattern **281** by an adhesive agent **383**, and the fixing pattern **164** is fixed to the spacer **385** by an adhesive agent **382**. The combination of the adhesive agent **382**, the spacer **385** and the adhesive agent **383** is an example of a bonding member.

(106) In order for the MLA **260** to sufficiently receive the light emitted from the VCSEL element **159**, it is desirable that the variation in the distance between the VCSEL chip **140** and the MLA **260** is $\pm 3\ \mu\text{m}$ or less. For example, in a case where the height of the VCSEL chip **140** is 250 μm and the distance between the face **141b** of the VCSEL chip **140** and the lower end of the microlens **262** is attempted to be set to 100 μm , the distance from the upper face of the base substrate **220** to the lower end of microlens **262** is 350 μm . For such a long distance, i.e., 350 μm , it is difficult to reduce the variation to $\pm 3\ \mu\text{m}$ or less with only the surface tension of the adhesive agent **282** such as a single piece of solder and the like.

(107) In this modification, the spacer **385** is provided. Therefore, the amounts of the adhesive agents **382** and **383** are smaller, and the variation in the distances is reduced by the surface tensions of the adhesive agents **382** and **383**, and bonding can be performed with high accuracy. For example, low temperature solders can be used as the adhesive agents **382** and **383**.

(108) Examples of materials of the spacer **385** include silicon (Si) and quartz. Si has the advantages in a low material cost and in the ease of processing. Since quartz has a co-efficient of thermal expansion that is close to the coefficient of thermal expansion of the substrate **141** of the VCSEL chip **140**, the quartz has an advantage in that the amount of variation in the distance between the VCSEL chip **140** and the MLA **260** can be reduced even when the VCSEL chip **140** generates heat during operation.

(109) The oscillation wavelength of the VCSEL element is not limited to 940 nm band, and may be, for example, 980 nm band, 1.3 μm band, or 1.5 μm band. The material constituting the VCSEL element is not limited, and AlGaInAs or GaInPAs may be used for the VCSEL element. Also, the

composition of each compound semiconductor layer is not particularly limited.

(110) Further, the material of MLA is not limited to quartz glass, and for example, borosilicate glass may be used. The radius of curvature of the microlens can be designed according to the refractive index of the material. The microlens may be provided on a side of the transparent substrate opposite to the VCSEL chip.

(111) The MLA bonding method is not limited to the self-alignment method. For example, bonding may be performed by a passive alignment method or an active alignment method. In the passive alignment method, for example, the MLA can be aligned using an alignment mark provided on the VCSEL chip or the base substrate and an alignment mark provided on the MLA. In the active alignment method, for example, the MLA can be adjusted to an optically appropriate position by moving the MLA in a state where the VCSEL chip is emitting light. When these bonding methods are employed, for example, an ultraviolet (UV) curable resin or a thermosetting resin can be used as the adhesive agent. The fixing patterns may not be used when the bonding is performed according to the self-alignment method.

(112) The VCSEL chip **140** is an individual drive type VCSEL chip that can individually drive each of the VCSEL elements **159**. However, the VCSEL chip used for the present disclosure may be a collective drive type VCSEL chip that collectively drives the VCSEL elements in the chip. In the collective drive type VCSEL chip, the number of second electrodes can be reduced. A surface emitting laser module including the collective drive type VCSEL chip can also achieve the effect of reducing the size of the VCSEL chip.

(113) Alternatively, an electrode on a mesa corresponding to each VCSEL element, for example, a p-side electrode, may be directly bonded, as a second electrode, to an electrode on the base substrate. In this case, it is not necessary to provide the second electrodes at the outside of the light emitting element unit of the VCSEL chip in the top view.

Third Embodiment

(114) Next, the third embodiment will be described. The third embodiment relates to a distance measuring device. A distance measuring device is an example of an optical device. FIG. **19** is a drawing illustrating a distance measuring device according to the third embodiment.

(115) A distance measuring device **400** according to the third embodiment includes a light projecting unit **410**, a light receiving unit **420**, a time measurement circuit **430**, and a control circuit **440**.

(116) The light projecting unit **410** includes, for example, a light source **411**, a light source driving circuit **412**, a light scanner **413**, a light scanner driving circuit **414**, a scan angle monitor **415**, and a projection lens **416**. The light source **411** includes a VCSEL module according to the first or second embodiment. The light source driving circuit **412** drives the light source **411** based on a driving signal output from the control circuit **440**. The light scanner **413** includes a MEMS (Micro Electro Mechanical System) mirror, a polygon mirror, or the like. The light scanner driving circuit **414** drives the light scanner **413** based on the driving signal output from the control circuit **440**. The VCSEL module of the light source **411** has a plurality of light emitting sub-regions. Each of the sub light emitting regions includes one or more VCSEL elements, and the VCSEL elements in each of the light emitting sub-regions are electrically connected in parallel. The sub light emitting regions are arranged one-dimensionally in the scanning direction (in the sub scanning direction) of the light scanner **413**, and can be driven individually. The VCSEL modules of the light source **411** are driven by the light source driving circuit **412** with, for example, a pulse current in the order of nanoseconds. The laser light emitted from the VCSEL element is converted into a desired beam profile by the projection lens **416** or the like as necessary, and thereafter, the light emission direction is determined by the light scanner **413** and the light is emitted to the outside of the distance measuring device **400**. The scanning angle of the light scanner **413** is measured by the scan angle monitor **415**, and the result is output to the control circuit **440**. The light scanner **413** and the projection lens **416** are an example of a second optical element.

(117) The laser light emitted to the outside of the distance measuring device **400** is reflected by a target object, returns back to the distance measuring device **400**, and reaches the light receiving unit **420**.

(118) The light receiving unit **420** includes, for example, a light receiving element **421**, a light receiving lens **422**, and a band pass filter **423**. The light receiving element **421** includes an APD (Avalanche Photo Diode) element of silicon. The light receiving lens **422** causes the light reaching the light receiving unit **420** to converge on the light receiving element **421**. The band pass filter **423** includes a dielectric multilayer and is designed to transmit only light in the range of the oscillation wavelength of the light source **411**. The band pass filter **423** can improve the S/N ratio of the signal.

(119) The light that reaches the light receiving element **421** is converted into an electric signal by the light receiving element **421** and is input to the time measurement circuit **430** through an amplifier **431** and a comparator **432** as necessary.

(120) The time measurement circuit **430** receives the driving signal of the light source **411** output from the control circuit **440** and the signal from the light receiving element **421**. The time measurement circuit **430** measures the delay time between these two signals and outputs the result to the control circuit **440**.

(121) The control circuit **440** converts the delay time from the time measurement circuit **430** into the wavelength of light.

(122) According to the distance measuring device **400**, two-dimensional distance information can be obtained by measuring the distance to the target object by sequentially emitting the laser light to the spatial area decomposed by the light emitting sub-regions of the VCSEL modules and the light scanner **413**. This distance measuring device **400** can be used for, for example, a LiDAR (Light Detection and Ranging).

(123) In addition to the distance measuring device light source, the surface emitting laser module according to the present disclosure can be used as an excitation light source for a solid-state laser. The surface emitting laser module can be used as a light source device such as a projector in combination with an optical element, such as a fluorescent body, that converts the wavelength of the emitted light from the surface emitting laser module. The surface emitting laser module can also be used as a light source device for sensing in combination with an optical element, such as, e.g., a lens, a mirror, or a diffraction grating, that diverge or converge the emitted light from the surface emitting laser module.

(124) The preferred embodiments and the like have been described in detail above, but the present invention is not limited to the above-described embodiments and the like, and various modifications and substitutions can be applied to the above embodiments and the like without departing from the scope described in the claims.

REFERENCE SIGNS LIST

(125) **100, 200** surface emitting laser module **120, 220** base substrate **140** VCSEL chip **150a, 150b** mesa **155** second electrode **157** first electrode **158** light emitting element unit **159** VCSEL element **160, 260** MLA **162** microlens **164, 181, 281** fixing pattern **182, 282, 382, 383** adhesive agent **385** spacer **400** distance measuring device **411** light source

CITATION LIST

Patent Literature

(126) [PTL 1] Japanese Unexamined Patent Application Publication No.2007-142425

(127) The present application is based on and claims the benefit of priority of Japanese Priority Application No. 2019-016353 filed on Jan. 31, 2019, the entire contents of which are hereby incorporated herein by reference.

Claims

1. A surface emitting laser module comprising: a base substrate; a surface emitting laser substrate mounted on the base substrate, the surface emitting laser substrate including a surface emitting laser element, and the surface emitting laser substrate having a first face facing the base substrate and a second face facing away from the base substrate; and an optical member facing the second face and including an optical element to receive light emitted from the second face of the surface emitting laser element, wherein the surface emitting laser element includes: a first semiconductor layer of a first conductivity type; a second semiconductor layer of a second conductivity type; a first electrode provided on the first face and connected to the first semiconductor layer; and a second electrode provided on the first face and connected to the second semiconductor layer, wherein the base substrate has a third face facing the first face of the surface emitting laser substrate, and includes: a third electrode provided on the third face and connected to the first electrode; and a fourth electrode provided on the third face and connected to the second electrode, wherein the first electrode and the second electrode are disposed away from a light emitting element structure comprising an array of a plurality of mesas and is to generate light in the surface emitting laser element, and wherein the second electrode and a current injection area of the plurality of mesas are connected by an interconnect.
2. The surface emitting laser module according to claim 1, wherein the surface emitting laser substrate is flip-chip mounted on the base substrate.
3. The surface emitting laser module according to claim 1, wherein the surface emitting laser element includes an active layer between the first semiconductor layer and the second semiconductor layer.
4. The surface emitting laser module according to claim 1, further comprising a bonding member bonding the optical member with the second face of the surface emitting laser substrate.
5. The surface emitting laser module according to claim 4, wherein, when viewed from a direction perpendicular to the second face of the surface emitting laser substrate, at least a part of the bonding member is included in an area in which the first electrode and the second electrode are included.
6. The surface emitting laser module according to claim 4, wherein, when viewed from a direction perpendicular to the second face of the surface emitting laser substrate, at least a part of the bonding member overlaps either the first electrode or the second electrode, or overlaps both of the first electrode and the second electrode.
7. The surface emitting laser module according to claim 1, further comprising a bonding member bonding the optical member with the third face of the base substrate.
8. The surface emitting laser module according to claim 7, wherein, when viewed from a direction perpendicular to the second face of the surface emitting laser substrate, the first electrode and the second electrode are disposed at a side of the surface emitting laser element relative to the bonding member.
9. The surface emitting laser module according to claim 7, wherein the bonding member includes a spacer interposed between the optical member and the base substrate.
10. An optical device comprising: the surface emitting laser module according to claim 1; and a second optical element to receive light emitted from the surface emitting laser module.
11. An optical device comprising: the surface emitting laser module according to claim 1; and a light receiving structure to receive light that is emitted by the surface emitting laser module and is reflected by or passing through a target object.
12. A surface emitting laser substrate having a first face and a second face opposite to the first face, the surface emitting laser substrate comprising: a surface emitting laser element to emit light from the second face, wherein the surface emitting laser element includes: a first semiconductor layer of a first conductivity type; a second semiconductor layer of a second conductivity type; a first electrode provided on the first face and connected to the first semiconductor layer; and a second

electrode provided on the first face and connected to the second semiconductor layer, wherein the first electrode and the second electrode are disposed away from a light emitting element structure comprising an array of a plurality mesas and is to generate light in the surface emitting laser element, and wherein the second electrode and a current injection area of the plurality of mesas are connected by an interconnect.

13. The surface emitting laser substrate according to claim 12, wherein the surface emitting laser element includes an active layer between the first semiconductor layer and the second semiconductor layer.

14. The surface emitting laser substrate according to claim 12, further comprising: a bonding area provided on the second face to be bonded with an optical element receiving light emitted from the surface emitting laser element.
