

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414369
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Lee; Tae-Won et al.

Display device

Abstract

Disclosed is a display device. The display device includes a substrate having an active area and a non-active area, a thin film transistor arranged on the active area of the substrate, at least two planarization layers arranged on the thin film transistor, signal links arranged on the non-active area of the substrate, and an outer cover layer spaced apart from the at least two planarization layers and configured to overlap upper and side surfaces of the signal links, thus preventing or reducing damage to the signal links.

Inventors: Lee; Tae-Won (Wonju-si, KR), Park; Jong-Chan (Paju-si, KR), Um; Hyun-Chul (Paju-si, KR)

Applicant: LG Display Co., Ltd. (Seoul, KR)

Family ID: 69621431

Assignee: LG Display Co., Ltd. (Seoul, KR)

Appl. No.: 18/218498

Filed: July 05, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230354645 A1	Nov. 02, 2023

Foreign Application Priority Data

KR	10-2018-0108411	Sep. 11, 2018
----	-----------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L27/12** (20060101); **H10D86/40** (20250101); **H10D86/60** (20250101); **H10K10/84** (20230101); **H10K50/84** (20230101); **H10K59/121** (20230101); **H10K59/131** (20230101); **H10K59/80** (20230101)

U.S. Cl.:

CPC **H10D86/451** (20250101); **H10D86/40** (20250101); **H10D86/60** (20250101); **H10K10/84** (20230201); **H10K50/84** (20230201); **H10K59/1213** (20230201); **H10K59/131** (20230201); **H10K59/8731** (20230201);

Field of Classification Search

CPC: H10K (59/1213); H10K (50/84); H10K (10/84); H01L (27/1214)

USPC: 257/72

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9082667	12/2014	Youn et al.	N/A	N/A
9122116	12/2014	Fujikawa	N/A	N/A
9214498	12/2014	Yun et al.	N/A	N/A
9293485	12/2015	Youn et al.	N/A	N/A
10734471	12/2019	Park et al.	N/A	N/A
10963076	12/2020	Choi et al.	N/A	N/A
2005/0077524	12/2004	Ahn et al.	N/A	N/A
2013/0168655	12/2012	Yun et al.	N/A	N/A
2014/0049449	12/2013	Park	29/841	H10K 59/128
2014/0146257	12/2013	Fujikawa	N/A	N/A
2014/0217397	12/2013	Kwak et al.	N/A	N/A
2014/0232956	12/2013	Kwon et al.	N/A	N/A
2014/0353670	12/2013	Youn et al.	N/A	N/A
2015/0287750	12/2014	Youn et al.	N/A	N/A
2016/0190225	12/2015	Kim et al.	N/A	N/A
2017/0125505	12/2016	Oh	N/A	N/A
2017/0277288	12/2016	Choi et al.	N/A	N/A
2017/0287995	12/2016	Kim et al.	N/A	N/A
2017/0331058	12/2016	Seo et al.	N/A	N/A
2017/0345882	12/2016	Nam et al.	N/A	N/A
2018/0033821	12/2017	Kim	N/A	H01L 27/124

2018/0102502	12/2017	Kim et al.	N/A	N/A
2018/0122881	12/2017	Shin et al.	N/A	N/A
2018/0122890	12/2017	Park et al.	N/A	N/A
2018/0151838	12/2017	Park et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
108123062	12/2017	CN	N/A
102012024538	12/2013	DE	N/A
2814074	12/2013	EP	N/A
2830095	12/2014	EP	N/A
3327786	12/2017	EP	N/A
2570795	12/2018	GB	N/A
2000-323715	12/1999	JP	N/A
2014-232300	12/2013	JP	N/A
10-2016-0013399	12/2015	KR	N/A
10-2016-0080042	12/2015	KR	N/A
10-2017-0113757	12/2016	KR	N/A
10-2018-0047536	12/2017	KR	N/A
10-2018-0047607	12/2017	KR	N/A
20180047607	12/2017	KR	H01L 27/12
10-2018-0078672	12/2017	KR	N/A
WO 2013/011678	12/2012	WO	N/A

OTHER PUBLICATIONS

Machine English Translation of KR 20180047607. (Year: 2018). cited by examiner
China National Intellectual Property Administration, Office Action, CN Patent Application No. 201910789135.3, Mar. 1, 2023, 14 pages. cited by applicant
German Patent and Trademark Office, Office Action, DE Patent Application No. 102019120820.3, Feb. 20, 2023, 13 pages. cited by applicant
Japan Patent Office, Decision of Refusal, JP Patent Application No. 2019-149225, Jan. 7, 2021, ten pages. cited by applicant
Japan Patent Office, Notice of Reasons for Refusal, JP Patent Application No. 2019-149225, Sep. 1, 2020, ten pages. cited by applicant
Japan Patent Office, Office Action, JP Patent Application No. 2022-041474, May 9, 2023, eight pages. cited by applicant
The Intellectual Property Office of the United Kingdom, Combined Search and Examination Report under Sections 17 and 18(3), GB Application No. 1912006.2, Feb. 17, 2020, seven pages. cited by applicant
United States Office Action, U.S. Appl. No. 16/533,698, Sep. 22, 2020, 16 pages. cited by applicant
United States Office Action, U.S. Appl. No. 17/220,523, Nov. 21, 2022, 12 pages. cited by applicant
Korean Intellectual Property Office, Office Action, Korean Patent Application No. 10-2018-0108411, Aug. 24, 2023, 11 pages. cited by applicant
Japan Patent Office, Notice of Allowance, Japanese Patent Application No. 2023-203710, Mar. 27, 2025, six pages. cited by applicant

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 17/220,523 filed Apr. 1, 2021 which is a divisional of U.S. patent application Ser. No. 16/533,698 filed on Aug. 6, 2019 which claims the benefit of Republic of Korea Patent Application No. 10-2018-0108411, filed on Sep. 11, 2018, each of which is incorporated by reference in its entirety.

BACKGROUND

Field of Technology

(1) The present disclosure relates to a display device, and more particularly, to a display device having high definition and high resolution.

Discussion of the Related Art

(2) Image display devices, which display various pieces of information on a screen, are a core technology in the age of information and communication and have been developed to satisfy thinness, light-weight, portability and high-performance trends. Therefore, an organic light emitting diode (OLED) display, which can reduce weight and volume to make up for drawbacks of a cathode ray tube (CRT), is now in the spotlight. Such an organic light emitting diode display is a self-luminous device and has advantages, such as low power consumption, high response speed, high luminous efficacy, high brightness and wide viewing angle. Such an organic light emitting diode display implements an image through a plurality of subpixels arranged in a matrix. Each of the subpixels includes a light emitting element, and a pixel circuit including a plurality of transistors to independently drive the light emitting element.

(3) As the organic light emitting diode display is developed to have high definition and high resolution, load applied to respective signal lines and respective electrodes is greatly increased and thus resistor-capacitor (RC) delay exerting a negative influence on image quality and driving characteristics is gradually increased. Particularly, signal delay due to RC load between the light emitting element and the transistor occurs and may thus cause difficulty in applying a driving signal to each subpixel.

SUMMARY

(4) Accordingly, the present disclosure is directed to a display device that substantially obviates one or more problems due to limitations and disadvantages of the related art.

(5) An object of the present disclosure is to provide a display device having high definition and high resolution.

(6) Additional advantages, objects, and features of the disclosure will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following. The objectives and other advantages may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

(7) To achieve these objects and other advantages and in accordance with the purpose of the disclosure, as embodied and broadly described herein, a display device includes a substrate having an active area and a non-active area, a thin film transistor arranged on the active area of the substrate, at least two planarization layers arranged on the thin film transistor, signal links arranged on the non-active area of the substrate, and a first outer cover layer configured to overlap upper and side surfaces of the signal links, thus realizing high definition and high resolution and preventing damage to the signal links and a protective film on the signal links.

(8) In some embodiments, the first outer cover layer is spaced apart from the at least two

planarization layers. In some embodiments, the at least two planarization layers include a first and second planarization layer. The first planarization layer is arranged on a protective film and is configured to cover the thin film transistor. The second planarization layer is arranged on the first planarization layer. In some embodiments, the display device includes a pixel connection electrode that is connected to a drain electrode of the thin film transistor and arranged between the first and second planarization layers. In some embodiments, the pixel connection electrode is formed of a material which is a same material as the drain electrode.

(9) In some embodiments, the signal links include a lower link and an upper link. The lower link is formed of a same material as a gate electrode of the thin film transistor and is coplanar with the gate electrode. The upper link is formed of a same material as a source electrode and the drain electrode of the thin film transistor. The upper link is coplanar with the source electrode and the drain electrode and is connected to the lower link. The first outer cover layer is formed of the same material as the first planarization layer and is arranged on the protective film. The protective film is arranged on the upper link. In some embodiments, the display device includes at least one link contact hole in an interlayer insulating film arranged between the source and drain electrodes and the gate electrode. The link contact hole exposes the lower link. The upper link is connected to the lower link through the at least one link contact hole. The first outer cover layer overlaps the at least one link contact hole.

(10) In some embodiments, the display device includes conductive pads, a light emitting element, an encapsulation unit, at least one dam, and a second outer cover layer. conductive pads connected to the signal links. The light emitting element is connected to the thin film transistor. The encapsulation unit is arranged on the light emitting element. The at least one dam is arranged between the conductive pads and the light emitting element. The second outer cover layer is arranged between the at least one dam and the conductive pads. In some embodiments, the encapsulation unit includes first and second inorganic encapsulation layers formed of an inorganic insulating material, and an organic encapsulation layer. In some embodiments, the second outer cover layer is formed on the signal links to have a greater line width than that of the signal links. In some embodiments, the signal links are formed of a same material as a source electrode and the drain electrode of the thin film transistor, and the second outer cover layer is formed of a same material as the pixel connection electrode so as to be in a same layer as the pixel connection electrode. In some embodiments, the display device includes a third outer cover layer that is formed on the second outer cover layer and has a greater line width than that of the second outer cover layer. The third outer cover layer is formed of a same material as the second planarization layer.

(11) In some embodiments, the display device includes high voltage supply lines including first and second high voltage supply lines connected through line contact holes passing through the protective film and the first planarization layer. In some embodiments, the display device includes a pixel connection electrode arranged between the first and second planarization layers. The first high voltage supply line is formed of a same material as source and drain electrodes of the thin film transistor so as to be coplanar with the source and drain electrodes, and the second high voltage supply line is formed of a same material as the pixel connection electrode so as to be coplanar with the pixel connection electrode.

(12) In some embodiments, the first outer cover layer includes a plurality of first outer cover layer portions corresponding to a plurality of signal links in the signal links respectively. In some embodiments, each of the plurality of first outer cover layer portions has a flat upper surface or a stepwise upper surface on the signal links.

(13) In still other embodiments, a display device includes a substrate, a thin film transistor, a conductive pad, a first link, a second link, and first outer cover layer. The substrate has an active area and a non-active area. The thin film transistor is in the active area of the substrate. The conductive pad is in the non-active area of the substrate. The first link is electrically connected to

the conductive pad is in the non-active area of the substrate. The second link has a first end electrically connected to an electrode of the thin film transistor in the active area of the substrate and has a second end electrically connected to the first link in the non-active area of the substrate. The first outer cover layer covers a top and one or more sides of a signal link region where the first link and the second link overlap from a plan view of the substrate.

(14) In some embodiments, the first link is in a first layer and the second link is in a second layer on the substrate.

(15) In some embodiments, the display device includes an interlayer insulating film between the first link and the second link. The first link and the second link are electrically connected through a hole in the interlayer insulating film.

(16) In some embodiments, the first link has a first width, the second link has a second width greater than the first width in the signal link region where the first link and the second link overlap, and the first outer cover layer has a third width greater than the second width.

(17) In some embodiments, the first link is formed of a same material and in a same layer as a gate electrode of the thin film transistor and the second link is formed of a same material and in a same layer as a source electrode and a drain electrode of the thin film transistor.

(18) In some embodiments, the display device includes a planarization layer that covers the thin film transistor. The first outer cover layer is formed of a same material as the planarization layer.

(19) In some embodiments, the display device includes a first planarization and a pixel connection electrode. The first planarization layer covers the thin film transistor. The pixel connection electrode is electrically connected to a drain electrode of the thin film transistor through a hole in the first planarization layer. The first outer cover layer is formed of a same material as the pixel connection electrode. In some embodiments, the substrate includes a second planarization layer and a second outer cover layer. The second planarization layer covers the pixel connection electrode and the first planarization layer. The second outer cover layer covers top and side surfaces of the of the first outer cover layer. The second outer cover layer is formed of a same material as the second planarization layer.

(20) In some embodiments, the display device includes a light emitting element, an encapsulation unit, and at least one dam. The light emitting element is in the active area and is connected to the thin film transistor. The encapsulation unit is arranged on the light emitting element. The at least one dam is arranged between the conductive pad and the light emitting element. The second outer cover layer is arranged between the at least one dam and the conductive pad.

(21) It is to be understood that both the foregoing general description and the following detailed description of the present disclosure are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The accompanying drawings, which are included to provide a further understanding of the disclosure and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the disclosure and together with the description serve to explain the principle of the disclosure.

In the drawings:

(2) FIG. 1 is a plan view illustrating an organic light emitting diode display in accordance with one embodiment;

(3) FIGS. 2A and 2B are cross-sectional views illustrating the organic light emitting diode display of FIG. 1, taken along line I-I' and line II-II' in accordance with some embodiments;

(4) FIG. 3 is a plan view illustrating an organic light emitting diode display having an outer cover layer differing from that of the light emitting diode display shown in FIG. 1 in accordance with one

embodiment;

(5) FIGS. 4A and 4B are cross-sectional views illustrating the organic light emitting diode display of FIG. 3, taken along line in accordance with some embodiments;

(6) FIGS. 5A and 5B are cross-sectional views illustrating an organic light emitting diode display having no outer cover layer according to a comparative example in accordance with some embodiments;

(7) FIGS. 6A and 6B are cross-sectional views illustrating an organic light emitting diode display having an outer cover layer in accordance with some embodiments;

(8) FIG. 7 is a plan view illustrating an organic light emitting diode display in accordance with an embodiment; and

(9) FIG. 8 is a cross-sectional view illustrating the organic light emitting diode display of FIG. 7, taken along line IV-IV' in accordance with an embodiment.

DETAILED DESCRIPTION

(10) Reference will now be made in detail to the preferred embodiments, examples of which are illustrated in the accompanying drawings.

(11) FIG. 1 is a plan view illustrating an organic light emitting diode display in accordance with one embodiment, and FIGS. 2A and 2B are cross-sectional views illustrating the organic light emitting diode display of FIG. 1, taken along line I-I' and line II-II'.

(12) The organic light emitting diode display shown in FIG. 1 and FIGS. 2A and 2B is divided into an active area AA, and a non-active area NA arranged at the perimeter of the active area AA.

(13) A plurality of subpixels is arranged in a matrix in the active area AA to display an image. Each subpixel includes a pixel driving circuit and a light emitting element 130 connected to the pixel driving circuit.

(14) The pixel driving circuit includes a switching transistor TS, a driving transistor TD and a storage capacitor Cst (not shown). The pixel driving circuit having a structure including two transistors TS and TD and one capacitor C is exemplarily described, without being limited thereto.

(15) The switching transistor Ts is turned on when a scan pulse is supplied to a scan line SL, and thus supplies a data signal supplied to a data line DL to the storage capacitor Cst and a gate electrode 102 of the driving transistor TD. For this purpose, the switching transistor TS includes, as exemplarily shown in FIG. 1, a gate electrode GE connected to the scan line SL, a source electrode SE connected to the data line DL, a drain electrode DE connected to the driving transistor TD, and a semiconductor layer ACT forming a channel between the source electrode SE and the drain electrode DE.

(16) The driving transistor TD controls current supplied from high voltage (VDD) supply lines VL to the light emitting element 130 in response to a data signal supplied to the gate electrode 102 of the driving transistor TD, thus adjusting an amount of light emitted from the light emitting element 130. Further, even if the switching transistor TS is turned off, the driving transistor TD supplies constant current by voltage charging the storage capacitor Cst until a data signal of a next frame is supplied and, thus, the light emitting element 130 maintains light emission.

(17) For this purpose, the driving transistor TD includes, as exemplarily shown in FIG. 1 and FIGS. 2A and 2B, a semiconductor layer 104 arranged on an active buffer layer 114, the gate electrode 102 overlapping the semiconductor layer 104 with a gate insulating film 112 disposed therebetween, and source and drain electrodes 106 and 108 formed on an interlayer insulating film 116 and contacting the semiconductor layer 104. In other words, it may be said that overlapping may refer to two elements occupying at least partially the same space in a plan view. It may be said that overlapping does not require direct physical contact between the two elements.

(18) The semiconductor layer 104 is formed of at least one of an amorphous semiconductor material, a polycrystalline semiconductor material or an oxide semiconductor material. The semiconductor layer 104 is formed on the active buffer layer 114. The semiconductor layer 104 includes a channel region, a source region and a drain region. The channel region overlaps the gate

electrode **102** with the gate insulating film **112** disposed therebetween and is formed between the source electrode **106** and the drain electrode **108**. The source region is conductively connected to the source electrode **106** through a source contact hole **110S** passing through the gate insulating film **112** and the interlayer insulating film **116**. The drain region is conductively connected to the drain electrode **108** through a drain contact hole **110D** passing through the gate insulating film **112** and the interlayer insulating film **116**. A multi-buffer layer **140** and the active buffer layer **114** are arranged between the semiconductor layer **104** and a substrate **101**. The multi-buffer layer **140** delays diffusion of moisture and/or oxygen permeating the substrate **101**. The active buffer layer **114** functions to protect the semiconductor layer **104** and to block various kinds of defects introduced from the substrate **101**.

(19) Here, the uppermost layer of the multi-buffer layer **140** contacting the active buffer layer **114** is formed of a material having different etching characteristics from the remaining layers of the multi-buffer layer **140**, the active buffer layer **114**, the gate insulating film **112** and the interlayer insulating film **116**. The uppermost layer of the multi-buffer layer **140** contacting the active buffer layer **114** is formed of one of SiN.sub.x and SiO.sub.x, and the remaining layers of the multi-buffer layer **140**, the active buffer layer **114**, the gate insulating film **112** and the interlayer insulating film **116** are formed of the other of SiN.sub.x and SiO.sub.x. For example, the uppermost layer of the multi-buffer layer **140** contacting the active buffer layer **114** is formed of SiN.sub.x, and the remaining layers of the multi-buffer layer **140**, the active buffer layer **114**, the gate insulating film **112** and the interlayer insulating film **116** are formed of SiO.sub.x.

(20) The gate electrode **102** is formed on the gate insulating film **112**, and overlaps the channel region of the semiconductor layer **104** with the gate insulating film **112** interposed therebetween. The gate electrode **102** is formed of a first conductive material having a single layer or multilayer structure using one selected from the group consisting of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu), or an alloy thereof.

(21) The source electrode **106** is connected to the source region of the semiconductor layer **104** exposed through the source contact hole **110S** passing through the gate insulating film **112** and the interlayer insulating film **116**. The drain electrode **108** is disposed opposite to the source electrode **106** and is connected to the drain region of the semiconductor layer **104** through the drain contact hole **110D** passing through the gate insulating film **112** and the interlayer insulating film **116**. The source and drain electrodes **106** and **108** are formed of a second conductive material having a single layer or multilayer structure using one selected from the group consisting of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu), or an alloy thereof.

(22) A pixel connection electrode **142** is arranged between first and second planarization layers **128** and **148**. The pixel connection electrode **142** is exposed through a first pixel contact hole **100** passing through a protective film **118** and the first planarization layer **128**, and is connected to the drain electrode **108**. The pixel connection electrode **142** is formed of a material having a low specific resistance which is the same as or similar to the drain electrode **108**. In other words, it may be said that a material having a low specific resistance refers to a material having a low resistivity. Herein it may be said that, a material having a low specific resistance may be a metal.

(23) The high voltage supply lines VL disposed in parallel with the data line DL include first and second high voltage supply lines VL1 and VL2 connected through line contact holes **180** passing through the protective film **118** and the first planarization layer **128**. The first high voltage supply line VL1 is formed of the same material as the source and drain electrodes **106** and **108** of the driving transistor TD so as to be coplanar (e.g., in a same layer) with the source and drain electrodes **106** and **108**, and the second high voltage supply line VL2 is formed of the same material as the pixel connection electrode **142** so as to be coplanar with the pixel connection electrode **142**. For example, the second high voltage supply line VL2 and the pixel connection

electrode **142** are formed of a conductive material having a single layer or multilayer structure using one selected from the group consisting of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu), or an alloy thereof. The conductive material may be referred to as the third conductive material herein.

(24) As such, the high voltage supply lines VL of the include the first and second high voltage supply lines VL1 and VL2 which are conductively connected through the line contact holes **180**, and thus, resistance of the high voltage supply lines VL may be reduced and an RC time constant may be reduced. Accordingly, delay of transmission of high voltage (VDD) from the high voltage supply lines VL to the source electrode **106** of the driving transistor TD may be prevented and thus high definition and high resolution may be realized.

(25) The light emitting element **130** includes an anode **132**, at least one light emitting stack **134** formed on the anode **132**, and a cathode **136** formed on the at least one light emitting stack **134**.

(26) The anode **132** is conductively connected to the pixel connection electrode **142** exposed through a second pixel contact hole **120** passing through the second planarization layer **148** arranged on the first planarization layer **128**.

(27) The anodes **132** of the respective subpixels are formed to be exposed by a bank **138**. Such a bank **138** may be formed of an opaque material (for example, a black-colored material) so as to prevent optical coherence between adjacent subpixels. In this case, the bank **138** includes a light-shielding material formed of at least one selected from the group consisting of a color pigment, an organic black pigment and carbon.

(28) The at least one light emitting stack **134** is formed on the anode **132** in a light emitting area prepared by the bank **138**. The at least one light emitting stack **134** is formed by stacking a hole-related layer, an organic light emitting layer and an electron-related layer on the anode **132** in regular order or in reverse order. Otherwise, the at least one light emitting stack **134** may include first and second light emitting stacks disposed opposite to each other with a charge generation layer interposed therebetween. In this case, an organic light emitting layer of one of the first and second light emitting stacks generates blue light, an organic light emitting layer of the other of the first and second light emitting stacks generates yellow-green light and, thus, white light is generated through the first and second light emitting stacks. White light generated by the at least one light emitting stack **134** is incident upon color filters (not shown) located on or under the at least one light emitting stack **134**, thus implementing a color image. Otherwise, without separate color filters, each light emitting stack **134** may generate color light corresponding to each subpixel, thus implementing a color image. That is, the light emitting stack **134** of the red (R) subpixel may generate red light, the light emitting stack **134** of the green (G) subpixel may generate green light, and the light emitting stack **134** of the blue (B) subpixel may generate blue light.

(29) The cathode **136** is formed opposite to the anode **132** with the at least one light emitting stack **134** disposed therebetween and is connected to low voltage (VSS) supply lines.

(30) Data pads DP connected to the data lines DL, scan pads SP connected to the scan lines SL, and power pads (not shown) connected to the low voltage (VSS) supply lines and the high voltage (VDD) supply lines are arranged in the non-active area NA. The data pads DP, the scan pads SP and the power pads may be arranged in the non-active area NA arranged at any one of one side and the other side of the substrate **101**, or the data pads DP, the scan pads SP and the power pads may be arranged in the non-active area NA arranged at different regions of the substrate **101**.

Arrangement of the data pads DP, the scan pads SP and the power pads is not limited to the structure shown in FIG. 1, and may be variously modified according to design specifications of the display.

(31) At least one conductive pad of the data pads DP, the scan pads SP or the power pads is connected to the corresponding signal line through a signal link. The signal link may include a lower link **122** and an upper link **124**, as exemplarily shown in FIGS. 1, 2A, and 2B. The signal link may be referred to herein as a "signal link region." The signal link may include a region where

the lower link **122** and the upper link **124** overlap from a plan view of the substrate **101**.

(32) The lower link **122** extends from one of the conductive pad and the signal line, and the upper link **124** extends from the other of the conductive pad and the signal line.

(33) The lower link **122** is exposed through at least one link contact hole **126** passing through at least one interlayer insulating film **116** arranged between the source and drain electrodes **106** and **108** and the gate electrode **102**, and is connected to the upper link **124**. The lower link **122** is formed of the same material as the gate electrode **102** of the driving transistor TD so as to be coplanar with the gate electrode **102** (for example, to be arranged on the gate insulating film **112**), and the upper link **124** is formed of the same material as the source and drain electrodes **106** and **108** of the driving transistor TD so as to be coplanar with the source and drain electrodes **106** and **108** (for example, to be arranged on the interlayer insulating film **116**).

(34) The protective film **118** formed of an inorganic insulating material is arranged on the upper link **124**, and an outer cover layer **146** (may be referred to herein as the first outer cover layer) formed of the same organic insulating material as the first planarization layer **128** is arranged on the protective film **118**.

(35) The outer cover layer **146** formed of the organic insulating material is formed to be spaced apart from the first and second planarization layers **128** and **148**. In other words, it may be said that 'spaced apart from' may refer to an arrangement where the two components are arranged such that they are not in physical contact. Therefore, inflow of moisture or oxygen from the outside into the light emitting element **130** through the outer cover layer **146** and the first and second planarization layers **128** and **148** is prevented, and thus damage to the light emitting element **130** may be prevented.

(36) The outer cover layer **146** may be formed to correspond to a plurality of signal links arranged on the substrate **101** one-to-many (in other words, it may be said that one outer cover layer corresponds to more than one signal link), as exemplarily shown in FIG. 1, or be formed to correspond to signal links one-to-one (in other words, it may be said that one outer cover layer corresponds to one signal link), as exemplarily shown in FIG. 3 and FIGS. 4A and 4B. In some embodiments a signal link refers to a conductive path between two components of the display device.

(37) The outer cover layer **146** may be formed to have a flat upper surface on the upper link **124**, as exemplarily shown in FIG. 4A, or be formed to have a stepwise upper surface so that the thickness of the outer cover layer **146** is decreased in a direction to the edge thereof, as exemplarily shown in FIG. 4B. The outer cover layer **146** having the stepwise upper surface may prevent a defect of the outer cover layer **146** caused by generation of stepped portions during a subsequent process of the outer cover layer **146**.

(38) The outer cover layer **146** is formed to overlap not only the link contact holes **126** but also the upper surface and the side surface of the upper link **124**. Particularly, the outer cover layer **146** is formed on the protective film **118** covering stepped portions generated by the link contact holes **126** and stepped portions generated by the side surfaces of the upper links **124** so as to overlap the link contact holes **126**.

(39) Therefore, embodiments may prevent loss of the protective film **118** and damage to the upper links **124** during a subsequent process of the first planarization layer **128**. This will be described in detail with reference to FIGS. 5A and 5B and FIGS. 6A and 6B.

(40) FIGS. 5A and 5B are cross-sectional views illustrating an organic light emitting diode display having no outer cover layer according to a comparative example, and FIGS. 6A and 6B are cross-sectional views illustrating an organic light emitting diode display having an outer cover layer according to an example.

(41) In the comparative example shown in FIGS. 5A and 5B, after lower links **122**, an interlayer insulating film **116**, upper links **124**, a protective film **118** and a first planarization layer **128** are sequentially formed, a pixel connection electrode **142** is formed in an active area. Here, during a

dry etching process for forming the pixel connection electrode **142**, a portion of the protective film **118** corresponding to a stepped portion generated by a link contact hole **126** can be removed. And, the upper link **124** can be exposed through the removed portion of the protective film **118** (region A). The exposed upper link **124** causes short-circuit with a conductive material of at least one of an anode **132** or a cathode **136** formed after formation of the pixel connection electrode **142**.

(42) Further, during a dry etching process for forming at least one of the pixel connection electrode **142** or the anode **132**, if the protective film **118** is lost (region B), the upper link **124** under the protective film **118** can be released or damaged. In this case, a contact defect between the lower link **122** and the upper link **124** occurs, and the material released from the upper link **124** can be moved to the active area by a wet etching solution during the etching process of the anode **132**. And, a defect of foreign substances can be occurred by the released material moved to the active area.

(43) Moreover, during the dry etching process for forming the pixel connection electrode **142**, a tip including a residue material **142A** of the pixel connection electrode **142** (region C) may be generated around the upper link **124** (referred to as a tip defect). The residue material **142A** of the pixel connection electrode **142** can be moved to the active area by the etching solution during the wet etching process of the anode **132**. And a defect of foreign substances can be occurred by the residue material **142A** moved to the active area.

(44) In contrast, in the example shown in FIGS. **6A** and **6B**, after lower links **122**, an interlayer insulating film **116**, upper links **124** and a protective film **118** are sequentially formed, a first planarization layer **128** and an outer cover layer **146** are simultaneously formed. Thereafter, a pixel connection electrode **142** is formed in an active area. During a dry etching process for forming the pixel connection electrode **142**, the outer cover layer **146** covers the protective film **118** on the upper links **124**. The outer cover layer **146** covers the protective film **118** at a stepped portion generated by a link contact hole **126** during the dry etching process for forming the pixel connection electrode **142**. Therefore, loss of the protective film **118** and exposure of the upper links **124** during the dry etching process for forming the pixel connection electrode **142** may be prevented or reduced. Accordingly, short-circuit between the upper link **124** and a conductive material of at least one of an anode **132** or a cathode **136**, a contact defect between the upper link **124** and a lower link **122**, and a defect due to foreign substances, caused by a conductive material of at least one of the upper link **124** or the pixel connection electrode **142**, may be prevented or reduced.

(45) FIG. **7** is a plan view illustrating an organic light emitting diode display in accordance with another embodiment, and FIG. **8** is a cross-sectional view illustrating the organic light emitting diode display of FIG. **7**, taken along line IV-IV'.

(46) The display shown in FIGS. **7** and **8** includes the same elements as the display shown in FIGS. **1** and **2** except that the display shown in FIGS. **7** and **8** further includes an encapsulation unit **150**, a plurality of dams **158** and a second outer cover layer **164**. Therefore, a detail description of the elements of the organic light emitting diode display in accordance with this embodiment, which are the same as those of the organic light emitting diode display in accordance with the former embodiment, will be omitted.

(47) The encapsulation unit **150** prevents or reduces external moisture or oxygen from permeating the light emitting elements **130**, which are vulnerable to external moisture or oxygen. For this purpose, the encapsulation unit **150** includes at least one inorganic encapsulation layer and at least one organic encapsulation layer. In some embodiments, the encapsulation unit **150** having a structure in which a first inorganic encapsulation layer **152**, an organic encapsulation layer **154** and a second inorganic encapsulation layer **156** are sequentially stacked will be exemplarily described.

(48) The first inorganic encapsulation layer **152** is formed on a substrate **101** provided with a cathode **136** formed thereon. The second inorganic encapsulation layer **156** is formed on the substrate **101** provided with the organic encapsulation layer **154** formed thereon, and the first

inorganic encapsulation layer **152** and the second inorganic encapsulation layer **156** are formed to surround the upper, lower and side surfaces of the organic encapsulation layer **154**. The first and second inorganic encapsulation layers **152** and **156** minimize or block permeation of external moisture or oxygen into a light emitting stack **134**. The first and second inorganic encapsulation layers **152** and **156** are formed of an inorganic insulating material which may be deposited at a low temperature, such as silicon nitride (SiN.sub.x), silicon oxide (SiO.sub.x), silicon oxynitride (SiON) or aluminum oxide (Al.sub.2O.sub.3). Therefore, since the first and second inorganic encapsulation layers **152** and **156** are deposited in a low-temperature atmosphere, damage to the light emitting stack **134**, which is vulnerable to a high-temperature atmosphere, during a deposition process of the first and second inorganic encapsulation layers **152** and **156** may be prevented or reduced.

(49) The organic encapsulation layer **154** serves as a buffer to damp stress between respective layers according to bending of the organic light emitting diode display, and strengthens planarization performance of the organic light emitting diode display. The organic encapsulation layer **154** is formed of a non-photosensitive organic insulating material, such as polycaprolactone (PCL), acrylic resin, epoxy resin, polyimide, polyethylene or silicon oxycarbide (SiOC), or a photosensitive organic insulating material, such as photoacryl, on the substrate **101** provided with the first inorganic encapsulation layer **152** formed thereon. If the organic encapsulation layer **154** is formed through an inkjet method, the dams **158** are arranged so as to prevent or reduce the organic encapsulation layer **154** in a liquid state from diffusing into the edge of the substrate **101**. The dams **158** are arranged more closely to the edge of the substrate **101** than the organic encapsulation layer **154**. The dams **158** may prevent or reduce the organic encapsulation layer **154** from diffusing to a pad region in which conductive pads arranged in the outermost region of the substrate **101** are arranged.

(50) The second outer cover layer **164** may be arranged in a region which may not be covered by the outer cover layer **146** shown in FIGS. **1** and **2**. For example, the second outer cover layer **164** is arranged in a region between the dams **158** and the conductive pads SP and DP, in which a thin film formed of an organic insulating material (e.g., usable as a moving path of external moisture or oxygen) may not be arranged. In some embodiments, the second outer cover layer **164** is formed instead of the outer cover layer **146**. In other embodiments, the second outer cover layer **164** is formed in addition to the outer cover layer **146**.

(51) The second outer cover layer **164** is formed through the same mask process as the pixel connection electrode **142**. That is, the second outer cover layer **164** may be formed of the third conductive material (e.g., the same material as the pixel connection electrode **142**) on the protective film **118** so as to be coplanar with the pixel connection electrode **142**. The second outer cover layer **164** is arranged on signal links **162** formed of a second conductive material (e.g., the same material as source and drain electrodes **106** and **108**). The signal links **162** may be a single line that electrically connects a conductive pad (e.g., a data pad) to a corresponding signal line. The second outer cover layer **164** has a line width w_2 that is greater than a line width w_1 of the signal links **162**. Because the second outer cover layer **164** has a wider line width than the signal links **162**, the second outer cover layer **164** covers the upper and side surfaces of the signal links **162**. Since the protective film **118** may be arranged over the signal links **162**, the second outer cover layer **164** may also be arranged over the protective film **118**. Accordingly, during an etching process for forming the second outer cover layer **164** and the pixel connection electrode **142**, the third conductive material of the second outer cover layer **164** covers the protective film **118** on the signal links **162**. Therefore, embodiments may prevent or reduce the loss of the protective film **118** arranged on the signal links **162**, damage to the signal links **162**, and tip defects of the third conductive material.

(52) A third outer cover layer **166** formed of the same material as a second planarization layer **148** is arranged on the second outer cover layer **164**. The third outer cover layer **166** has a greater line

width than the line width w_2 of the second outer cover layer **164** so as to cover the side and upper surfaces of the second outer cover layer **164**. Such a third outer cover layer **166** is formed to have a thickness less than that of the second planarization layer **148**, and thus, generation of stepped portions due to the third outer cover layer **166** may be reduced. Accordingly, during a process of pressing a signal transmission film (for example, a flexible printed circuit (FPC) or a tape carrier package (TCP)) to the conductive pads adjacent to the third outer cover layer **166**, a pressing process defect due to a thickness of the third outer cover layer **166** may be prevented or reduced.

(53) Although the former embodiment exemplarily describes the structure including the outer cover layer **146** and the latter embodiment exemplarily describes the structure including the second and third cover layers **164** and **166**, yet another embodiment may describe a structure including both the outer cover layer **146** and the second and third cover layers **164** and **166**.

(54) Further, the present disclosure exemplarily describes the structure, in which the outer cover layer **146** is arranged on the signal links **122** and **124** having the link contact holes **126**, and the second and third outer cover layers **164** and **166** are arranged on the signal links **162** having no link contact holes **126**, but the disclosure is not limited thereto. The second and third outer cover layers **164** and **166** may be arranged on the signal links **122** and **124** having the link contact holes **126**, and the outer cover layer **146** may be arranged on the signal links **162** having no link contact holes **126**.

(55) Also, although the present disclosure exemplarily describes the structure in which the outer cover layer **146** and the second and third outer cover layers **164** and **166** are arranged on the signal links **122**, **124** and **162** connected to the data pads DP, the outer cover layer **146** and the second and third outer cover layers **164** and **166** may be arranged on signal links connected to the scan pads SP and/or the power pads.

(56) Moreover, although the present disclosure exemplarily describes the organic light emitting diode display, the disclosure may be applied to all display devices including thin film transistors.

(57) As apparent from the above description, in a display device in accordance with the present disclosure, a drain electrode of a thin film transistor is connected to an anode of a light emitting element through a pixel connection electrode formed of a material having a low specific resistance. Therefore, the display device in accordance with the present disclosure may reduce signal delay due to RC load between the light emitting element and the thin film transistor and thus realize high definition and high resolution.

(58) Further, the display device in accordance with the present disclosure includes an outer cover layer overlapping a stepped portion generated by the side surface of a signal link and a stepped portion generated by a link contact hole interconnecting the signal links. Therefore, the display device in accordance with the present disclosure may prevent or reduce the loss of a protective film covering the signal links, release of the signal links, and tip defects of the third conductive material during an etching process for forming the pixel connection electrode.

(59) It will be apparent to those skilled in the art that various modifications and variations can be made in the present disclosure without departing from the spirit or scope of the invention. Thus, it is intended that the present disclosure cover the modifications and variations provided they come within the scope of the appended claims and their equivalents.

Claims

1. A display device comprising: a substrate having an active area and a non-active area; a multi-buffer layer on the substrate; an active buffer layer on the multi-buffer layer; a thin film transistor in the active area of the active buffer layer; a passivation layer that covers the thin film transistor; a first planarization layer directly covering the passivation layer in the active area; an anode electrode on the first planarization layer and electrically connected to the thin film transistor; a light emitting stack on the anode electrode; a cathode electrode on the light emitting stack; an encapsulation part

arranged on the light emitting stack, the encapsulation part including: a first inorganic encapsulation layer, a second inorganic encapsulation layer, an organic encapsulation layer between the first inorganic encapsulation layer and the second inorganic encapsulation layer, and formed through an ink jet method, a conductive pad in the non-active area of the substrate; a first link electrically connected to the conductive pad in the non-active area of the substrate; a second link overlapping the first link in a signal link region and connected to the thin film transistor in the active area of the substrate; a first outer cover layer covering a top and one or more sides of the signal link region; at least one dam arranged between the conductive pad and the light emitting stack; wherein the first outer cover layer comprises a same material as the first planarization layer, wherein the first outer cover layer is spaced apart from the first planarization layer and disconnected from the first planarization layer, wherein the second link overlaps the at least one dam, wherein the thin film transistor includes a source electrode and a drain electrode formed on the active buffer layer, and wherein the second link comprises a same material as the source electrode and the drain electrode.

2. The display device of claim 1, wherein the first outer cover layer fully covers the first link and the second link in the signal link region.

3. The display device of claim 1, wherein the first inorganic encapsulation layer and the second inorganic encapsulation layer cover the at least one dam while being in contact with each other, and the organic encapsulation layer is confined by the at least one dam.

4. The display device of claim 1, wherein the first link is in a first layer and the second link is in a second layer on the first layer.

5. The display device of claim 1, further comprising: an interlayer insulating film extending from the active area and positioned between the first link and the second link, and wherein the first link and the second link are electrically connected through a hole in the interlayer insulating film.

6. The display device of claim 1, wherein: the first link has a first width, the second link has a second width that is greater than the first width in the signal link region, and the first outer cover layer has a third width that is greater than the second width.

7. The display device of claim 1, wherein: the first link comprises a same material and is in a same layer as a gate electrode of the thin film transistor, and the second link is in a same layer as a source electrode and a drain electrode of the thin film transistor.

8. The display device of claim 7, wherein each of the second link, the source electrode, and a drain electrode of the thin film transistor includes a multi-layer comprising an alloy of titanium, aluminum, titanium.

9. The display device of claim 1, wherein a pixel connection electrode is electrically connected to a drain electrode of the thin film transistor through a hole in the first planarization layer.

10. The display device of claim 1, wherein further comprising: a second planarization layer that covers a pixel connection electrode and the first planarization layer; and a second outer cover layer that covers top and side surfaces of the first outer cover layer, wherein the second outer cover layer is formed of a same material as the second planarization layer.

11. The display device of claim 1, wherein the passivation layer extends from the active area to the signal link region and further covers the first link and the second link, wherein the first outer cover layer directly covers the passivation layer in the signal link region.

12. The display device of claim 1, wherein the passivation layer has a constant thickness in the signal link region, and wherein the first outer cover layer has a stepwise upper surface whose thickness becomes thinner toward an edge in the signal link region.
