

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12389664
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Lin; Shih-Yao et al.

Transistor gates and methods of forming thereof

Abstract

A device includes a semiconductor substrate and a first gate stack over the semiconductor substrate, the first gate stack being between a first gate spacer and a second gate spacer. The device further includes a second gate stack over the semiconductor substrate between the first gate spacer and the second gate spacer and a dielectric material separating the first gate stack from the second gate stack. The dielectric material is at least partially between the first gate spacer and the second gate spacer, a first width of an upper portion of the dielectric material is greater than a second width of a lower portion of the dielectric material, and a third width of an upper portion of the first gate spacer is less than a fourth width of a lower portion of the first gate spacer.

Inventors: Lin; Shih-Yao (New Taipei, TW), Lin; Chih-Han (Hsinchu, TW), Jang; Shu-Uei (Hsinchu, TW), Tsai; Ya-Yi (Hsinchu, TW), Ku; Shu-Yuan (Zhubei, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Family ID: 76853504

Assignee: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Appl. No.: 18/401866

Filed: January 02, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240153827 A1	May. 09, 2024

Related U.S. Application Data

continuation parent-doc US 17869590 20220720 US 11894277 child-doc US 18401866
division parent-doc US 16871514 20200511 US 11437287 20220906 child-doc US 17869590
us-provisional-application US 62968681 20200131

Publication Classification

Int. Cl.: **H10D84/03** (20250101); **H01L21/28** (20250101); **H10D30/01** (20250101); **H10D64/01** (20250101); **H10D64/66** (20250101); **H10D84/01** (20250101); **H10D84/85** (20250101)

U.S. Cl.:

CPC **H10D84/038** (20250101); **H01L21/28123** (20130101); **H10D30/0243** (20250101); **H10D64/017** (20250101); **H10D64/021** (20250101); **H10D64/671** (20250101); **H10D84/0172** (20250101); **H10D84/0184** (20250101); **H10D84/0193** (20250101); **H10D84/853** (20250101);

Field of Classification Search

CPC: H01L (21/823864); H01L (21/28123); H01L (21/823821); H01L (21/823828); H01L (27/0924); H01L (29/4983); H01L (29/66545); H01L (29/6656); H01L (29/6681); H10D (30/0243); H10D (84/0181); H10D (84/0188)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9064932	12/2014	Pham et al.	N/A	N/A
9105490	12/2014	Wang et al.	N/A	N/A
9236267	12/2015	De et al.	N/A	N/A
9236300	12/2015	Liaw	N/A	N/A
9406804	12/2015	Huang et al.	N/A	N/A
9443769	12/2015	Wang et al.	N/A	N/A
9520482	12/2015	Chang et al.	N/A	N/A
9548366	12/2016	Ho et al.	N/A	N/A
9576814	12/2016	Wu et al.	N/A	N/A
9831183	12/2016	Lin et al.	N/A	N/A
9859386	12/2017	Ho et al.	N/A	N/A
10043879	12/2017	Kim et al.	N/A	N/A
10163640	12/2017	Hsieh	N/A	H01L 21/823437
10930749	12/2020	Jeon et al.	N/A	N/A
11437287	12/2021	Lin	N/A	H01L 27/088
2011/0104894	12/2010	Kim et al.	N/A	N/A
2018/0138092	12/2017	Lee et al.	N/A	N/A
2018/0190652	12/2017	Ching et al.	N/A	N/A
2018/0240891	12/2017	Yu et al.	N/A	N/A
2018/0308949	12/2017	Lin et al.	N/A	N/A
2019/0067120	12/2018	Ching et al.	N/A	N/A
2019/0103325	12/2018	Huang	N/A	H01L 21/32134
2019/0164765	12/2018	Yeoh et al.	N/A	N/A
2019/0221431	12/2018	Hsieh et al.	N/A	N/A
2019/0252383	12/2018	Lin	N/A	H01L 21/823431
2019/0304976	12/2018	Zhu et al.	N/A	N/A
2019/0305099	12/2018	Jo et al.	N/A	N/A

2019/0363009	12/2018	Joe et al.	N/A	N/A
2019/0378914	12/2018	Huang et al.	N/A	N/A
2020/0083220	12/2019	Park et al.	N/A	N/A
2020/0083222	12/2019	Kim et al.	N/A	N/A
2020/0194277	12/2019	Dai et al.	N/A	N/A
2021/0111280	12/2020	Yang et al.	N/A	N/A
2021/0166977	12/2020	Wu et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
106409913	12/2016	CN	N/A
110600471	12/2018	CN	N/A
02018124814	12/2018	DE	N/A
20110047879	12/2010	KR	N/A
20180053803	12/2017	KR	N/A
20180079160	12/2017	KR	N/A
20190049315	12/2018	KR	N/A
20190055774	12/2018	KR	N/A
20190112910	12/2018	KR	N/A
20200050424	12/2019	KR	N/A

Primary Examiner: Enad; Christine A

Attorney, Agent or Firm: Slater Matsil, LLP

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE (1) This application is a continuation of U.S. application Ser. No. 17/869,590, filed Jul. 20, 2022, which is a divisional of U.S. application Ser. No. 16/871,514, filed on May 11, 2020, now U.S. Pat. No. 11,437,287, which claims the benefit of U.S. Provisional Application No. 62/968,681, filed on Jan. 31, 2020, which application is hereby incorporated herein by reference.

BACKGROUND

(1) Semiconductor devices are used in a variety of electronic applications, such as, for example, personal computers, cell phones, digital cameras, and other electronic equipment. Semiconductor devices are typically fabricated by sequentially depositing insulating or dielectric layers, conductive layers, and semiconductor layers of material over a semiconductor substrate, and patterning the various material layers using lithography to form circuit components and elements thereon.

(2) The semiconductor industry continues to improve the integration density of various electronic components (e.g., transistors, diodes, resistors, capacitors, etc.) by continual reductions in minimum feature size, which allow more components to be integrated into a given area. However, as the minimum features sizes are reduced, additional problems arise that should be addressed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description

when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. **1A** and **1B** illustrate examples of FinFETs in a three-dimensional view, in accordance with some embodiments.

(3) FIGS. **2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12A, 12B, 13A, 13B, 14A, 14B, 14C, 14D, 14E, 15A, 15B, 16A, 16B, 17A, 17B, 18A, 18B, 19A, 19B, 20A, 20B, 20C, 20D, 21A, 21B, 22A, 22B, 22C, 22D, 22E, 23A, 23B, 23C, 24A, 24B, 25A, 25B, 26A, 26B, 26C, 27, 28A, 28B, 29A, 29B, 30A, 30B, 31A, 31B, 32A, and 32B** are cross-sectional and top-down views of intermediate stages in the manufacturing of FinFETs, in accordance with some embodiments.

(4) FIGS. **33A, 33B, 34A, 34B, 35A, 35B, 36A, 36B, 36C, 36D, 37A, 37B, 38A, and 38B** are cross-sectional and top-down views of intermediate stages in the manufacturing of FinFETs, in accordance with some alternative embodiments.

DETAILED DESCRIPTION

(5) The following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(6) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(7) Various embodiments are described herein as applied to a fin field effect transistor (FinFET). Embodiments may be applied to other transistor technologies, including NanosheetFET (NSFET, including gate all around field effect transistors (GAAFETs), nanowire FETs, nanosheet FETs, and the like), or the like.

(8) In various embodiments, a dielectric material may be used to separate metal gates of adjacent transistors. The dielectric material may be formed by patterning an opening in a dummy gate stack or a metal gate stack and filling the dielectric material in the opening. In various embodiments, an upper portion of the opening may be widened, thereby improving a gap fill window of the dielectric material. For example, a small critical dimension may result in voids in the dielectric material, and these voids may be subsequently filled with undesirable materials (e.g., a metal gate material in cut dummy gate processes). By widening a gap fill window for the dielectric material, these voids can be reduced or eliminated. Further a lower portion of the opening may not be widened, and an effective gate width of the adjacent gate stacks may be maintained. In some embodiments, widening the upper portion of the opening may be achieved one or more cycles of treatment and etching processes. Accordingly, an atomic layer etch (ALE) type process may be achieved to control effective gate width and enlarge the dielectric material gap fill window. Manufacturing defects can be reduced, and device performance can be improved.

(9) FIGS. **1A** and **1B** illustrates examples of a device **10** and device **20**, respectively, in a three-dimensional view, in accordance with some embodiments. Each of the devices **10** and **20** comprises

FinFETs and are similar where like reference numerals indicate like elements. Portions of the devices **10** and **20** are cut away to illustrate underlying features (e.g., features outlined with dashed lines). The devices **10** and **20** each comprises fins **52** on a substrate **50** (e.g., a semiconductor substrate). Isolation regions **56** are disposed in the substrate **50**, and the fins **52** protrudes above and from between neighboring isolation regions **56**. Although the isolation regions **56** are described/illustrated as being separate from the substrate **50**, as used herein the term “substrate” may be used to refer to just the semiconductor substrate or a semiconductor substrate inclusive of isolation regions. Additionally, although the fins **52** is illustrated as a single, continuous material as the substrate **50**, the fin **52** and/or the substrate **50** may comprise a single material or a plurality of materials. In this context, the fins **52A** refers to the portion extending between the neighboring isolation regions **56**. As illustrated in FIG. **1A**, the device **10** further includes a dummy fin **52'** between adjacent fins **52**. The dummy fin **52'** is optional and may be omitted, such as in the device **20** as illustrated by FIG. **1B**.

(10) A gate dielectric layer **92** is along sidewalls and over a top surface of the fins **52**, gate electrodes **94** are over the gate dielectric layer **92**, and a gate mask layer **96** is over the gate electrodes **94**. The gate dielectric layer **92**, gate electrodes **94**, and gate mask layer **96** may also be disposed on sidewalls of the dummy channel regions **52'**. One or more layers of gate spacers **86** may be on sidewalls of the gate dielectric layer **92**, the gate electrodes **94**, and the gate mask layer **96**. Source/drain regions **82** are disposed in opposite sides of the fin **52A** with respect to the gate dielectric layer **92**, the gate electrodes **94**, and the gate mask layer **96**. The dummy fin **52'** may be disposed between and physically separate adjacent source/drain regions **82**. The source/drain regions **82** may also extend from a recessed portion of the fin **52A**.

(11) Dielectric material **38** extend through the gate mask layers **96** into the gate electrodes **94**. In the device **10** of FIG. **1A**, the dielectric material **38** may extend to the dummy fin **52'**, and a combination of the dielectric material **38** and the dummy fin **52'** may isolate gate electrodes of adjacent FinFETs (see e.g., FIG. **30A**). In the device **20** of FIG. **1B**, the dielectric material **38** may extend to isolation regions **56** to isolate gate electrodes of adjacent FinFETs (see e.g., FIG. **32A**). A contact etch stop layer (CESL) **87** is disposed over the isolation regions **56**, and a dielectric layer **88** is disposed over the CESL **87**. The dielectric layer **88** may further surround the source/drain regions **82**, portions of the dummy fin **52'** (if present), the gate mask layer **96**, the gate dielectric layer **92**, and the gate electrodes **94**.

(12) FIGS. **1A** and **1B** further illustrate reference cross-sections that are used in later figures. Cross-section A-A is along a longitudinal axis of the gate electrode **94** and in a direction, for example, perpendicular to the direction of current flow between the source/drain regions **82** of the FinFET. Cross-section B-B is perpendicular to cross-section A-A and is along a longitudinal axis of the fin **52** and in a direction of, for example, a current flow between the source/drain regions **82** of the FinFET. Cross-section B-B extends through a source/drain region of the FinFET. Cross-section C-C is parallel to cross-section A-A and extends through the source/drain region of the FinFET. Subsequent figures refer to these reference cross-sections for clarity. Cross-section D-D is parallel to cross-section B-B. In FIG. **1A**, cross-section D-D extends through a dummy fin of the FinFET, and in FIG. **1B**, cross-section D-D extends through an analogous location of the FinFET as FIG. **1A**.

(13) Some embodiments discussed herein are discussed in the context of FinFETs formed using a gate-last process. In other embodiments, a gate-first process may be used. Also, some embodiments contemplate aspects used in planar devices, such as planar FETs, in NSFETs, or the like.

(14) FIGS. **2** through **38B** are cross-sectional views of intermediate stages in the manufacturing of FinFETs, in accordance with some embodiments. FIGS. **2** through **11**, **12A**, **13A**, **14A**, **15A**, **16A**, **17A**, **18A**, **19A**, **21A**, **24A**, **25A**, **26A**, **27**, **28A**, **29A**, **30A**, **31A**, **32A**, **33A**, **34A**, **35A**, **36A**, **37A**, and **38A** illustrate reference cross-section A-A illustrated in FIGS. **1A/1B**, except for multiple fins/FinFETs. FIGS. **12B**, **13B**, **14B**, **15B**, **16B**, **24B**, **25B**, **26B**, **26C**, **28B**, **29B**, **30B**, **31B**, **32B**,

37B, and 38B are illustrated along a similar cross-section B-B illustrated in FIGS. 1A/1B, except for multiple fins/FinFETs. FIGS. 14C, 14D, and 14E are illustrated along reference cross-section C-C illustrated in FIG. 1, except for multiple fins/FinFETs. FIGS. 17B, 18B, 19B, 20B, 21B, 22A, 23A, 23B, 23C, 33B, 34B, 35B, and 36B are illustrated along reference cross-section D-D illustrated in FIGS. 1A/1B, except for multiple fins/FinFETs.

(15) In FIG. 2, a substrate 50 is provided. The substrate 50 may be a semiconductor substrate, such as a bulk semiconductor, a semiconductor-on-insulator (SOI) substrate, or the like, which may be doped (e.g., with a p-type or an n-type dopant) or undoped. The substrate 50 may be a wafer, such as a silicon wafer. Generally, an SOI substrate is a layer of a semiconductor material formed on an insulator layer. The insulator layer may be, for example, a buried oxide (BOX) layer, a silicon oxide layer, or the like. The insulator layer is provided on a substrate, typically a silicon or glass substrate. Other substrates, such as a multi-layered or gradient substrate may also be used. In some embodiments, the semiconductor material of the substrate 50 may include silicon; germanium; a compound semiconductor including silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including silicon-germanium, gallium arsenide phosphide, aluminum indium arsenide, aluminum gallium arsenide, gallium indium arsenide, gallium indium phosphide, and/or gallium indium arsenide phosphide; or combinations thereof.

(16) The substrate 50 has a region 50N and a region 50P. The region 50N can be for forming n-type devices, such as NMOS transistors, e.g., n-type FinFETs. The region 50P can be for forming p-type devices, such as PMOS transistors, e.g., p-type FinFETs. The region 50N may be physically separated from the region 50P (as illustrated by divider 51), and any number of device features (e.g., other active devices, doped regions, isolation structures, etc.) may be disposed between the region 50N and the region 50P.

(17) A hard mask 53 is deposited on the substrate 50. The hard mask 53 may be used to define a pattern of subsequently formed semiconductor fins. In some embodiments, the hard mask is deposited using physical vapor deposition (PVD), chemical vapor deposition (CVD), atomic layer deposition (ALD), or the like. The hard mask 53 may comprise silicon oxide, silicon nitride, silicon oxynitride, a metal oxide, a metal nitride, multilayers thereof, or the like. For example, although only one hard mask layer is illustrated, a multilayer structure (e.g., a layer of silicon oxide on a layer of silicon nitride) may be formed as the hard mask 53.

(18) FIGS. 3 through 32B illustrate various additional steps in the manufacturing of embodiment devices. FIGS. 3 through 32B illustrate features in either of the region 50N and the region 50P. For example, the structures illustrated in FIGS. 3 through 32B may be applicable to both the region 50N and the region 50P. Differences (if any) in the structures of the region 50N and the region 50P are described in the text accompanying each figure.

(19) FIGS. 3 through 7 illustrate cross-sectional views (e.g., along cross-section A-A of FIG. 1A) of manufacturing semiconductor fins and dummy fins according to various embodiments. The formation of dummy fins is optional and may be omitted in other embodiments (e.g., as illustrated by FIG. 1B). In FIG. 3, fins 52A and 52B are formed in the substrate 50. The fins 52A/52B are semiconductor strips. The fins 52A/52B include a fin 52B between fins 52A. As will be described in subsequent figures, the fin 52B may be optionally removed and replaced with a dummy fin 52' (see FIG. 6).

(20) In some embodiments, the fins 52A may be formed in the substrate 50 by etching trenches in the substrate 50. The etching may be any acceptable etch process, such as a reactive ion etch (RIE), neutral beam etch (NBE), the like, or a combination thereof. The etch may be anisotropic.

(21) The fins may be patterned by any suitable method. For example, the fins may be patterned using one or more photolithography processes, including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller

than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over a substrate and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers may then be used to pattern the fins. In some embodiments, the mask (or other layer) may remain on the fins 52A/52B.

(22) In FIG. 4, an insulation material 54 is formed over the substrate 50 and between neighboring fins 52A/52B. The insulation material 54 may be an oxide, such as silicon oxide, a nitride, the like, or a combination thereof, and may be formed by a high density plasma chemical vapor deposition (HDP-CVD), a flowable CVD (FCVD) (e.g., a CVD-based material deposition in a remote plasma system and post curing to make it convert to another material, such as an oxide), the like, or a combination thereof. Other insulation materials formed by any acceptable process may be used. In the illustrated embodiment, the insulation material 54 is silicon oxide formed by a FCVD process. An anneal process may be performed once the insulation material is formed. In an embodiment, the insulation material 54 is formed such that excess insulation material 54 covers the fins 52A/52B. Although the insulation material 54 is illustrated as a single layer, some embodiments may utilize multiple layers. For example, in some embodiments a conformal liner (not shown) may first be formed along a surface of the substrate 50 and the fins 52A/52B. Thereafter, a fill material, such as those discussed above may be formed over the liner.

(23) After deposition, a removal process is applied to the insulation material 54 to remove excess insulation material 54 over the fins 52A/52B. In some embodiments, a planarization process such as a chemical mechanical polish (CMP), an etch-back process, combinations thereof, or the like may be utilized. The planarization process exposes the fins 52A/52B such that top surfaces of the fins 52A/52B and the insulation material 54 are level after the planarization process is complete. In embodiments in which mask 53 remains on the fins 52A/52B, the planarization process may expose the mask 53 or remove the mask 53 such that top surfaces of the mask or the fins 52A/52B, respectively, and the insulation material 54 are level after the planarization process is complete.

(24) In FIG. 5, at least a portion of the fin 52B is removed using an acceptable etching process, for example. Thus, an opening 55 is formed in the insulation material 54 between the fins 52A. In subsequent processes, a dummy channel region may be formed in the opening 55. The fin 52B may be completely removed or a portion of the fin 52B may remain under the opening 55.

(25) In FIG. 6, a dummy fin 52' is formed in the opening 55. The dummy fin 52' may comprise one or more layers of a silicon-based material (e.g., SiN, SiON, SiOCN, SiC, SiOC, SiO.sub.2, or the like), a metal-based material (e.g., a metal oxide, metal nitride, or the like such as TaN, TaO, HfO, or the like), and/or the like. Although FIG. 6 illustrates the dummy fin 52' as being a single material, the dummy fin 52' may comprise multiple layers of materials, which may be stacked vertically and/or horizontally. For example, in some embodiments, a first layer of the dummy fin 52' may line sidewalls and a lateral surface of a second layer of the dummy fin 52'. As a further example, a third layer of the dummy fin 52' may be disposed on top of the second layer of the dummy fin 52'. In some embodiments, a width W of the dummy fin 52' may be in the range of about 5 Å to about 500 Å.

(26) The dummy fin 52' may be formed using one or more deposition processes, such as CVD, plasma enhanced CVD (PECVD), plasma enhanced ALD (PEALD), ALD, PVD, or the like. In embodiments where the dummy fin 52' comprises a multilayer structure, forming the dummy fin 52' may also include one or more etch back and/or planarization steps before additional material layer(s) of the dummy fin 52' are deposited. Further, the dummy fin 52' may be deposited to initially cover the insulation material 54, and a planarization, etch back, or the like process may be used to remove excess portions of the dummy fin 52' and expose the insulation material 54.

(27) In FIG. 7, the insulation material 54 is recessed to form Shallow Trench Isolation (STI) regions 56. The insulation material 54 is recessed such that upper portions of fins 52A and the

dummy fin 52' protrude from between neighboring STI regions 56. Further, the top surfaces of the STI regions 56 may have a flat surface as illustrated, a convex surface, a concave surface (such as dishing), or a combination thereof. The top surfaces of the STI regions 56 may be formed flat, convex, and/or concave by an appropriate etch. The STI regions 56 may be recessed using an acceptable etching process, such as one that is selective to the material of the insulation material 54 (e.g., etches the material of the insulation material 54 at a faster rate than the material of the fins 52). For example, an oxide removal using, for example, dilute hydrofluoric (dHF) acid may be used. Recessing the insulation material 54 may use a process that is selectively etches the insulation material 54 compared to the dummy fin 52' (if present).

(28) The process described with respect to FIGS. 2 through 7 is just one example of how the fins 52A may be formed. In some embodiments, the fins may be formed by an epitaxial growth process. For example, a dielectric layer can be formed over a top surface of the substrate 50, and trenches can be etched through the dielectric layer to expose the underlying substrate 50. Homoepitaxial structures can be epitaxially grown in the trenches, and the dielectric layer can be recessed such that the homoepitaxial structures protrude from the dielectric layer to form fins. Additionally, in some embodiments, heteroepitaxial structures can be used for the fins 52A. For example, the fins 52A in FIG. 7 can be recessed, and a material different from the fins 52A may be epitaxially grown over the recessed fins 52A. In such embodiments, the fins 52A comprise the recessed material as well as the epitaxially grown material disposed over the recessed material. In an even further embodiment, a dielectric layer can be formed over a top surface of the substrate 50, and trenches can be etched through the dielectric layer. Heteroepitaxial structures can then be epitaxially grown in the trenches using a material different from the substrate 50, and the dielectric layer can be recessed such that the heteroepitaxial structures protrude from the dielectric layer to form the fins 52A. In some embodiments where homoepitaxial or heteroepitaxial structures are epitaxially grown, the epitaxially grown materials may be in situ doped during growth, which may obviate prior and subsequent implantations although in situ and implantation doping may be used together.

(29) Still further, it may be advantageous to epitaxially grow a material in region 50N (e.g., an NMOS region) different from the material in region 50P (e.g., a PMOS region). In various embodiments, upper portions of the fins 52A may be formed from silicon-germanium ($\text{Si.sub.xGe.sub.1-x}$, where x can be in the range of 0 to 1), silicon carbide, pure or substantially pure germanium, a III-V compound semiconductor, a II-VI compound semiconductor, or the like. For example, the available materials for forming III-V compound semiconductor include, but are not limited to, indium arsenide, aluminum arsenide, gallium arsenide, indium phosphide, gallium nitride, indium gallium arsenide, indium aluminum arsenide, gallium antimonide, aluminum antimonide, aluminum phosphide, gallium phosphide, and the like.

(30) Further in FIG. 7, appropriate wells (not shown) may be formed in the fins 52A and/or the substrate 50. In some embodiments, a P well may be formed in the region 50N, and an N well may be formed in the region 50P. In some embodiments, a P well or an N well are formed in both the region 50N and the region 50P.

(31) In the embodiments with different well types, the different implant steps for the region 50N and the region 50P may be achieved using a photoresist or other masks (not shown). For example, a photoresist may be formed over the fins 52A and the STI regions 56 in the region 50N. The photoresist is patterned to expose the region 50P of the substrate 50, such as a PMOS region. The photoresist can be formed by using a spin-on technique and can be patterned using acceptable photolithography techniques. Once the photoresist is patterned, an n-type impurity implant is performed in the region 50P, and the photoresist may act as a mask to substantially prevent n-type impurities from being implanted into the region 50N, such as an NMOS region. The n-type impurities may be phosphorus, arsenic, antimony, or the like implanted in the region to a concentration of equal to or less than 10^{18} cm^{-3} , such as between about 10^{16} cm^{-3} and about 10^{18} cm^{-3} . After the implant, the photoresist is removed, such as by

an acceptable ashing process.

(32) Following the implanting of the region **50P**, a photoresist is formed over the fins **52A** and the STI regions **56** in the region **50P**. The photoresist is patterned to expose the region **50N** of the substrate **50**, such as the NMOS region. The photoresist can be formed by using a spin-on technique and can be patterned using acceptable photolithography techniques. Once the photoresist is patterned, a p-type impurity implant may be performed in the region **50N**, and the photoresist may act as a mask to substantially prevent p-type impurities from being implanted into the region **50P**, such as the PMOS region. The p-type impurities may be boron, boron fluoride, indium, or the like implanted in the region to a concentration of equal to or less than 10^{18} cm^{-3} , such as between about 10^{16} cm^{-3} and about 10^{18} cm^{-3} . After the implant, the photoresist may be removed, such as by an acceptable ashing process.

(33) After the implants of the region **50N** and the region **50P**, an anneal may be performed to repair implant damage and to activate the p-type and/or n-type impurities that were implanted. In some embodiments, the grown materials of epitaxial fins may be in situ doped during growth, which may obviate the implantations, although in situ and implantation doping may be used together.

(34) In the embodiment of FIG. 7, the dummy fin **52'** is illustrated as having a top surface that is substantially level (e.g., within manufacturing tolerances) with a top surface of the fins **52A**. For example, a height **H1** that the fins **52A** extend above the STI regions **56** is equal to a height **H2** that the dummy fin **52'** extends above the STI regions **56**. Other configurations are also possible. For example, the height **H1** may be less than or greater than the height **H2**, and a top surface of the dummy fin **52'** may be higher than or lower than a top surface of the fins **52A**.

(35) FIGS. 3 through 7 illustrate just one example of how dummy fins **52'** may be formed. Other methods are also possible. For example, FIGS. 8 through 10 illustrate intermediate steps of forming dummy fin **52'** in a device **15** according to alternative embodiments. In FIGS. 8 through 10, like reference numbers indicate like elements formed using like processes as the features described above in FIGS. 3 through 7. In FIGS. 8, fins **52** are formed extending from a substrate **50** using a similar process as described above in FIG. 2, for example. A hard mask **53**, is used to pattern the fins **52**, and may remain on the fins **52**.

(36) As also illustrated by FIG. 8, an insulation material **54** is deposited over and along sidewalls of the fins **52**. The insulation material **54** may be deposited using a conformal process, which only partially fills a space between the fins **52**. As a result of the deposition process, the opening **55** is defined between the fins **52** and over the insulation material **54**. One or more materials may be subsequently filled in the opening **55** for forming a dummy fin **52'**

(37) In FIG. 9, a dummy fin **52'** is formed in the opening **55**. The dummy fin **52'** may be disposed between fins **52**, and the dummy fin **52'** may be embedded in the insulation material **54**. For example, the insulation material **54** may contact a bottom surface and sidewalls of the dummy fin **52'**. Forming the dummy fin **52'** may be performed using a similar process as described above with respect to FIG. 6.

(38) In FIG. 10, the insulation material **56** is etched back to expose sidewalls of the fins **52**, expose sidewalls of the dummy fin **52'**, and define STI region **56**. Etching back the insulation material **54** may be performed using a similar process as described above with respect to FIG. 7. Accordingly, a method of forming the dummy fin **52'** may be completed according to alternative embodiments. Subsequent description of additional processes may be applied to either the device **10** (as illustrated by FIG. 7) or the device **15** (as illustrated by FIG. 10).

(39) FIGS. 11 through 31B illustrate cross-sectional views of additional steps of manufacturing the device **10**. It should be understood that these steps may also be applied to the device **15** (as illustrated by FIG. 10) or the device **20** (see FIG. 1B). In FIG. 11, a dummy dielectric layer **60** is formed on the fins **52A** and the dummy fin **52'** in the device **10**. The dummy dielectric layer **60** may be, for example, silicon oxide, silicon nitride, a combination thereof, or the like, and may be deposited or thermally grown according to acceptable techniques.

(40) A dummy gate layer **62** is formed over the dummy dielectric layer **60**, and a mask layer **64** is formed over the dummy gate layer **62**. The dummy gate layer **62** may be deposited over the dummy dielectric layer **60** and then planarized, such as by a CMP. The mask layer **64** may be deposited over the dummy gate layer **62**. The dummy gate layer **62** may be a conductive or non-conductive material and may be selected from a group including amorphous silicon, polycrystalline-silicon (polysilicon), poly-crystalline silicon-germanium (poly-SiGe), metallic nitrides, metallic silicides, metallic oxides, and metals. The dummy gate layer **62** may be deposited by physical vapor deposition (PVD), CVD, sputter deposition, or other techniques known and used in the art for depositing the selected material. The dummy gate layer **62** may be made of other materials that have a high etching selectivity from the etching of isolation regions.

(41) The mask layer **64** may include, for example, silicon nitride, silicon oxynitride, or the like. In this example, a single dummy gate layer **62** and a single mask layer **64** are formed across the region **50N** and the region **50P**. It is noted that the dummy dielectric layer **60** is shown covering only the fins **52A** for illustrative purposes only. In some embodiments, the dummy dielectric layer **60** may be deposited such that the dummy dielectric layer **60** covers the STI regions **56**, extending between the dummy gate layer **62** and the STI regions **56**.

(42) FIGS. **12A** through **16B** illustrate additional immediate stages of manufacture. In FIGS. **12A** through **16B**, figures that end in “A” are illustrated along the respective cross-section A-A of FIGS. **1A** and **1B**, and Figures that end in “B” are illustrated along the respective cross-section B-B of FIGS. **1A** and **1B**. FIGS. **14C**, **14D**, and **14E** are illustrated along respective cross-section C-C of FIGS. **1A** and **1B**.

(43) In FIGS. **12A** and **12B**, the mask layer **64** (see FIG. **11**) may be patterned using acceptable photolithography and etching techniques to form masks **74**. The pattern of the masks **74** then may be transferred to the dummy gate layer **62**. In some embodiments (not illustrated), the pattern of the masks **74** may also be transferred to the dummy dielectric layer **60** by an acceptable etching technique to form dummy gates **72**. The dummy gates **72** cover respective channel regions **58** of the fins **52A**. The dummy gates **72** also cover top surfaces and sidewalls of the dummy fin **52'**. The pattern of the masks **74** may be used to physically separate each of the dummy gates **72** from adjacent dummy gates. The dummy gates **72** may also have a lengthwise direction substantially perpendicular to the lengthwise direction of respective epitaxial fins **52A**.

(44) Further in FIGS. **12A** and **12B**, gate seal spacers **80** can be formed on exposed surfaces of the dummy gates **72**, the masks **74**, and/or the fins **52A**/dummy fin **52'**. A thermal oxidation or a deposition followed by an anisotropic etch may form the gate seal spacers **80**. The gate seal spacers **80** may be formed of silicon oxide, silicon nitride, silicon oxynitride, or the like.

(45) After the formation of the gate seal spacers **80**, implants for lightly doped source/drain (LDD) regions (not explicitly illustrated) may be performed. In the embodiments with different device types, similar to the implants discussed above in FIG. **6**, a mask, such as a photoresist, may be formed over the region **50N**, while exposing the region **50P**, and appropriate type (e.g., p-type) impurities may be implanted into the exposed fins **52A** in the region **50P**. The mask may then be removed.

(46) Subsequently, a mask, such as a photoresist, may be formed over the region **50P** while exposing the region **50N**, and appropriate type impurities (e.g., n-type) may be implanted into the exposed fins **52A** in the region **50N**. The mask may then be removed. The n-type impurities may be the any of the n-type impurities previously discussed, and the p-type impurities may be the any of the p-type impurities previously discussed. The lightly doped source/drain regions may have a concentration of impurities of from about 10^{15} cm^{-3} to about 10^{19} cm^{-3} . An anneal may be used to repair implant damage and to activate the implanted impurities.

(47) In FIGS. **13A** and **13B**, gate spacers **86** are formed on the gate seal spacers **80** along sidewalls of the dummy gates **72** and the masks **74**. The gate spacers **86** may be formed by conformally depositing an insulation material and subsequently anisotropically etching the insulation material.

The insulation material of the gate spacers **86** may be silicon oxide, silicon nitride, silicon oxynitride, silicon carbonitride, a combination thereof, or the like.

(48) It is noted that the above disclosure generally describes a process of forming spacers and LDD regions. Other processes and sequences may be used. For example, fewer or additional spacers may be utilized, different sequence of steps may be utilized (e.g., the gate seal spacers **80** may not be etched prior to forming the gate spacers **86**, yielding “L-shaped” gate seal spacers, spacers may be formed and removed, and/or the like. Furthermore, the n-type and p-type devices may be formed using a different structures and steps. For example, LDD regions for n-type devices may be formed prior to forming the gate seal spacers **80** while the LDD regions for p-type devices may be formed after forming the gate seal spacers **80**.

(49) In FIGS. **14A** through **14E** epitaxial source/drain regions **82** are formed in the fins **52A**. The source/drain regions **82** may exert stress in the respective channel regions **58**, thereby improving performance. The epitaxial source/drain regions **82** are formed in the fins **52A** such that each dummy gate **72** is disposed between respective neighboring pairs of the epitaxial source/drain regions **82**. In some embodiments the epitaxial source/drain regions **82** may extend into, and may also penetrate through, the fins **52A**. In some embodiments, the gate spacers **86** are used to separate the epitaxial source/drain regions **82** from the dummy gates **72** by an appropriate lateral distance so that the epitaxial source/drain regions **82** do not short out subsequently formed gates of the resulting FinFETs.

(50) The epitaxial source/drain regions **82** in the region **50N**, e.g., the NMOS region, may be formed by masking the region **50P**, e.g., the PMOS region, and etching source/drain regions of the fins **52A** in the region **50N** to form recesses in the fins **52A**. Then, the epitaxial source/drain regions **82** in the region **50N** are epitaxially grown in the recesses. The epitaxial source/drain regions **82** may include any acceptable material, such as appropriate for n-type FinFETs. For example, if the fin **52A** is silicon, the epitaxial source/drain regions **82** in the region **50N** may include materials exerting a tensile strain in the channel region **58**, such as silicon, silicon carbide, phosphorous doped silicon carbide, silicon phosphide, or the like. The epitaxial source/drain regions **82** in the region **50N** may have surfaces raised from respective surfaces of the fins **52A** and may have facets.

(51) The epitaxial source/drain regions **82** in the region **50P**, e.g., the PMOS region, may be formed by masking the region **50N**, e.g., the NMOS region, and etching source/drain regions of the fins **52A** in the region **50P** are etched to form recesses in the fins **52A**. Then, the epitaxial source/drain regions **82** in the region **50P** are epitaxially grown in the recesses. The epitaxial source/drain regions **82** may include any acceptable material, such as appropriate for p-type FinFETs. For example, if the fin **52A** is silicon, the epitaxial source/drain regions **82** in the region **50P** may comprise materials exerting a compressive strain in the channel region **58**, such as silicon-germanium, boron doped silicon-germanium, germanium, germanium tin, or the like. The epitaxial source/drain regions **82** in the region **50P** may also have surfaces raised from respective surfaces of the fins **52A** and may have facets.

(52) The epitaxial source/drain regions **82** and/or the fins **52A** may be implanted with dopants to form source/drain regions, similar to the process previously discussed for forming lightly-doped source/drain regions, followed by an anneal. The source/drain regions may have an impurity concentration of between about 10^{19} cm.⁻³ and about 10^{21} cm.⁻³. The n-type and/or p-type impurities for source/drain regions may be any of the impurities previously discussed. In some embodiments, the epitaxial source/drain regions **82** may be in situ doped during growth.

(53) As a result of the epitaxy processes used to form the epitaxial source/drain regions **82** in the region **50N** and the region **50P**, upper surfaces of the epitaxial source/drain regions have facets which expand laterally outward beyond sidewalls of the fins **52A**. Gate spacers **86** are formed covering a portion of the sidewalls of the fins **52A** that extend above the STI regions **56** thereby

blocking the epitaxial growth. In some other embodiments, the spacer etch used to form the gate spacers **86** may be adjusted to remove the spacer material to allow the epitaxially grown region to extend to the surface of the STI region **56**.

(54) In embodiments with the dummy fin **52'**, adjacent source/drain regions **82** remain separated after the epitaxy process is completed as illustrated by FIG. **14C**. For example, the source/drain regions **82** may grow to physically contact the dummy fin **52'**, which physically separates adjacent source/drain regions **82** from each other. Thus, adjacent epitaxial source/drain regions **82** may be prevented from merging and inadvertently shorted out.

(55) In other embodiments (e.g., the device **20** of FIG. **1B**), the dummy fin **52'** may not be formed. In such embodiments, the facets of the epitaxial source/drain regions **82** cause adjacent source/drain regions **82** of a same FinFET to merge as illustrated by FIG. **14D**. In other embodiments, adjacent source/drain regions **82** remain separated after the epitaxy process is completed as illustrated by FIG. **14E**. In the embodiments illustrated in FIGS. **14C**, **14D**, and **14E**, gate spacers **86** are formed covering a portion of the sidewalls of the fins **52** that extend above the STI regions **56** thereby blocking the epitaxial growth. In some other embodiments, the spacer etch used to form the gate spacers **86** may be adjusted to remove the spacer material to allow the epitaxially grown region to extend to the surface of the STI region **56**.

(56) In FIGS. **15A** and **15B**, a first interlayer dielectric (ILD) **88** is deposited over the structure illustrated in FIGS. **14A** and **14B**. The first ILD **88** may be formed of a dielectric material, and may be deposited by any suitable method, such as CVD, plasma-enhanced CVD (PECVD), or FCVD. Dielectric materials may include phospho-silicate glass (PSG), boro-silicate glass (BSG), boron-doped phospho-silicate glass (BPSG), undoped silicate glass (USG), or the like. Other insulation materials formed by any acceptable process may be used. In some embodiments, a contact etch stop layer (CESL) **87** is disposed between the first ILD **88** and the epitaxial source/drain regions **82**, the masks **74**, and the gate spacers **86**. The CESL **87** may comprise a dielectric material, such as, silicon nitride, silicon oxide, silicon oxynitride, or the like, having a different etch rate than the material of the overlying first ILD **88**.

(57) In FIGS. **16A** and **16B**, a planarization process, such as a CMP, may be performed to level the top surface of the first ILD **88** with the top surfaces of the dummy gates **72** or the masks **74**. The planarization process may also remove the masks **74** on the dummy gates **72**, and portions of the gate seal spacers **80** and the gate spacers **86** along sidewalls of the masks **74**. After the planarization process, top surfaces of the dummy gates **72**, the gate seal spacers **80**, the gate spacers **86**, and the first ILD **88** are level. Accordingly, the top surfaces of the dummy gates **72** are exposed through the first ILD **88**. In some embodiments, the masks **74** may remain, in which case the planarization process levels the top surface of the first ILD **88** with the top surface of the masks **74**.

(58) FIGS. **17A** through **21B** illustrate additional immediate stages of forming a dielectric material in the dummy gate **72** to separate gates of adjacent transistors. In FIGS. **17A** through **21B**, figures that end in "A" are illustrated along the respective cross-section A-A of FIGS. **1A** and **1B**, and Figures that end in "B" are illustrated along the respective cross-section D-D of FIGS. **1A** and **1B**.

(59) In FIGS. **17A** and **17B**, an opening **30** is patterned in the dummy gate **72**. In some embodiments, the opening **30** may be aligned with and disposed directly over the dummy fin **52'**. The opening **30** may be formed in the dummy gate **72** through a combination of photolithography and etching, for example. The opening **30** may expose sidewalls of the gate spacers (e.g., the gate seal spacers **80**/gate spacers **86**, see FIG. **17B**). A depth that the opening **30** extends may be controlled by tuning one or more parameters of the etching (e.g., etch time, or the like).

(60) In some embodiments, etching the opening **30** in the dummy gate **72** includes a plasma process, such as a plasma etch, a remote plasma process, a radical etch, or the like. An etching gas used during the plasma process may comprise Cl.sub.2, HBr, CF.sub.4, CHF.sub.3, CH.sub.2F.sub.2, CH.sub.3F, C.sub.4F.sub.6, BCl.sub.3, SF.sub.6, H.sub.2, combination thereof, or

the like. The plasma process may further include flowing a passivation gas over the device **10** for tuning (e.g., increasing) etch selectivity between the dummy gate **72** and other features of the device **10**. Embodiment passivation gases may comprise N.sub.2, O.sub.2, CO.sub.2, SO.sub.2, CO, SiCl.sub.4, combinations thereof, or the like. One or more carrier gases may also be used during the plasma process, such as, Ar, He, Ne, combinations thereof, or the like. Further, the plasma process may be performed with a plasma source power in the range of about 10 W to about 3000 W, with a bias power in the range of about 0 W to about 3000 W, at a pressure of about 1 mTorr to about 800 mTorr, with a gas mixture flow rate of about 10 sccm to about 5000 sccm, or the like.

(61) In some embodiments, etching the opening **30** in the dummy gate **72** includes a wet etch process (sometimes referred to as a wet clean). Embodiment etchants that may be used during the wet etch process may include HF, F.sub.2, combinations thereof, or the like. The wet etch process may further include flowing an assisted etch chemical over the device **10** for tuning (e.g., increasing) etch selectivity between the dummy gate **72** and other features of the device **10**. Embodiment assisted etch chemicals may comprise H.sub.2SO.sub.4, HCl, HBr, NH.sub.3, combinations thereof, or the like. Deionized water (DIW), alcohol, acetone, or the like may be used as a solvent for mixing the etchant and/or the assisted etch chemical during the wet etch process.

(62) In FIGS. **18A** and **18B**, a treatment process **32** is applied to the device **10**, such as to sidewalls and a bottom surface of the opening **30**. The treatment process **32** may form passivation regions **34** and **36** on sidewalls and a bottom surface of the opening **30**. The passivation region **34** may be formed in the dummy gate **72**, and the passivation region **36** may be formed in the gate spacers (e.g., the gate seal spacers **80** and/or the gate spacers **86**). Further although not explicitly illustrated, the treatment process **32** may further form passivation regions in other exposed surfaces of the wafer **10**, such as upper surfaces of the gate dummy gate **72** and upper surfaces of the first ILD **88**. Such passivation regions may be removed in subsequent processing steps.

(63) The treatment process **32** may be a conversion process that converts an exposed portion of the dummy gate **72** into the passivation region **34** and converts an exposed portion of the gate spacer (e.g., the gate seal spacers **80** and optionally the gate spacers **86**) into the passivation region **36**. The treatment process **32** may be performed in-situ (e.g., in a same process chamber) or ex-situ (e.g., in a different process chamber) of the etching process to form the opening **30**. A respective thickness of each of the passivation region **34** and the passivation layer **36** may be in the range of about 2 Å to about 300 Å.

(64) In some embodiments, the treatment process **32** includes a plasma process, such as a plasma implantation, or the like. A passivation gas used during the plasma process may comprise N.sub.2, O.sub.2, CO.sub.2, SO.sub.2, CO, combination thereof, or the like. The plasma process may further include flowing an additional gas, such as a carbon-based (CH.sub.4), a silicon-based gas (e.g., SiCl.sub.4), combinations thereof, or the like, to help form the passivation regions **34** and **36**. Further, the plasma process may be performed with a plasma source power in the range of about 10 W to about 3000 W, with a bias power in the range of about 0 W to about 3000 W, at a pressure of about 1 mTorr to about 800 mTorr, with a gas mixture flow rate of about 10 sccm to about 5000 sccm, or the like.

(65) In some embodiments, the treatment process **32** is a non-plasma, dry chemical treatment using a treatment gas, such as, HF, NF.sub.3, CH.sub.4, combinations thereof, or the like. In some embodiments, the treatment process **32** is a wet treatment process, which uses a solution comprising deionized water (DIW), O.sub.3, CO.sub.2, HF, HCl, NH.sub.3, combinations thereof, or the like. In some embodiments, the treatment process **32** is a deposition process that reacts with existing materials of the dummy gate **72** and the gate spacers and also deposits a dielectric material (e.g., SiN, SiON, SiCON, SiC, SiOC, SiO.sub.2, SiC, combinations thereof, or the like) on surfaces of the opening **30**. In such embodiments, the passivation regions **34** and **36** include the reacted areas of the dummy gate **72**, the reacted areas of the gate spacers, and the deposited dielectric

material. Embodiment deposition processes may include an ALD process, a CVD process, combinations thereof, or the like.

(66) Because a material of the dummy gate **72** is different than material(s) of the gate spacers (e.g., the gate seal spacers **80**/gate spacers **86**), the treated region **34** may have a different material composition than the treated region **36**. For example, in embodiments where the treatment process **32** comprises using nitrogen and the gate spacers comprise oxygen, the passivation region **34** may comprise silicon and nitrogen while the passivation region **36** may comprise silicon, oxygen, and nitrogen. As another example where the treatment process **32** comprises using oxygen and the gate spacers comprise nitrogen, the passivation region **34** may comprise silicon and oxygen while the passivation region **36** may comprise silicon, oxygen, and nitrogen. As another example where the treatment process **32** comprises using nitrogen and the gate spacers comprise nitrogen, a nitrogen concentration of the passivation region **34** may be lower than a nitrogen concentration of the passivation region **36**. As another example where the treatment process **32** comprises using oxygen and the gate spacers comprise oxygen, an oxygen concentration of the passivation region **34** may be lower than an oxygen concentration of the passivation region **36**. Accordingly, the treatment process **32** forms two different passivation regions **34** and **36**, and etch selectivity can be achieved between the passivation regions **34** and **36**. Etch selectivity can also be achieved between the passivation region **36** and remaining portions of the gate spacers.

(67) In FIGS. **19A** and **19B**, an etch process is applied to the dummy gate **72**, which extends the opening **30** further towards the dummy fin **52'** (if present) and the semiconductor substrate **50**. In some embodiments, the opening **30** may be extended to expose the dummy fin **52'** or the semiconductor substrate **50**.

(68) The etch process may be selective between a material of the passivation region **36** and a material of the gate spacers (e.g., the gate seal spacers **80**) such that the etch process removes the passivation region **36**. For example, the etch process may remove the material of the passivation region **36** at a greater rate than the material of the gate spacers. As a result and as illustrated in FIG. **19B**, an upper portion of the opening **30** may have a width **W1** that is greater than a width **W2** of a lower portion of the opening **30**.

(69) Further, the etch process may be a directional process, which removes the passivation region **34** from bottom surfaces of the recess **30** without significantly removing the passivation region **34** from sidewalls of the recess **30**. In some embodiments, the etch process may be selective between a material of the passivation regions **34** and **36** so that the material of the passivation region **36** is removed from sidewalls of the opening **30** without significantly removing the passivation region **34** from sidewalls of the opening **30**. As a result, an effective gate width of the dummy gate **72** (and corresponding replacement metal gate) can be maintained, thereby improving device performance of the resultant device.

(70) In some embodiments, removing the passivation region **36** and expanding the opening **30** includes a plasma process, such as a plasma etch, a remote plasma process, a radical etch, or the like. An etching gas used during the plasma process may comprise Cl.sub.2, HBr, CF.sub.4, CHF.sub.3, CH.sub.2F.sub.2, CH.sub.3F, C.sub.4F.sub.6, BCl.sub.3, SF.sub.6, H.sub.2, combination thereof, or the like. The plasma process may further include flowing a passivation gas over the device **10** for tuning (e.g., increasing) etch selectivity between the dummy gate **72** and other features of the device **10**. Embodiment passivation gases may comprise N.sub.2, O.sub.2, CO.sub.2, SO.sub.2, CO, SiCl.sub.4, combinations thereof, or the like. One or more carrier gases may also be used during the plasma process, such as, Ar, He, Ne, combinations thereof, or the like. Further, the plasma process may be performed with a plasma source power in the range of about 10 W to about 3000 W, with a bias power in the range of about 0 W to about 3000 W, at a pressure of about 1 mTorr to about 800 mTorr, with a gas mixture flow rate of about 10 sccm to about 5000 sccm, or the like.

(71) In some embodiments, removing the passivation region **36** and expanding the opening **30**

includes a wet etch process (sometimes referred to as a wet clean). Embodiment etchants that may be used during the wet etch process may include HF, F.sub.2, combinations thereof, or the like. The wet etch process may further include flowing an assisted etch chemical over the device **10** for tuning (e.g., increasing) etch selectivity between the dummy gate **72** and other features of the device **10**. Embodiment assisted etch chemicals may comprise H.sub.2SO.sub.4, HCl, HBr, NH.sub.3, combinations thereof, or the like. Deionized water (DIW), alcohol, acetone, or the like may be used as a solvent for mixing the etchant and/or the assisted etch chemical during the wet etch process.

(72) Although FIGS. **18A** through **19B** illustrates one treatment and etch cycle being applied to the opening **30** to expose the dummy fin **52'**, any multiple treatment and etch cycles may be performed. For example, the steps described with respect to FIGS. **18A** through **19B** may be repeated any number of times until the dummy fin **52'** is exposed and the opening **30** has a desired profile. By repeating the treatment process and etch process described above, an atomic layer etch type process may be achieved to form an opening with an expanded upper portion.

(73) In FIGS. **20A** and **20B**, the opening **30** is filled with a dielectric material **38**. The dielectric material **38** may be deposited by PVD, CVD, ALD, PECVD, or the like. The dielectric material **38** may initially be deposited to overfill the opening **30** and cover top surfaces of the dummy gate **72** and the first ILD **88**. Subsequently, a planarization process (e.g., CMP, or the like) may be performed to remove excess dielectric material **38** from above the dummy gate **72** and the first ILD **88**.

(74) In the device **10** comprising the dummy fin **52'**, the dielectric material **38** in combination of with the dummy fin **52'** separates the dummy gate **72** into different regions (e.g., regions **72A** and **72B**). In the device **20**, which does not include the dummy fin **52'**, the dielectric material **38** alone separates the dummy gate **72** into different regions **72A** and **72B** (see FIGS. **21A** and **21B**). In the device **20**, the dielectric material **38** extends to and contacts the semiconductor substrate **50**. The regions **72A** and **72B** may correspond to locations of different transistor devices, for example. Thus, the dielectric material **38** and the dummy fin **52'** (if present) may provide isolation between adjacent FinFETs.

(75) As a result of widening upper portions of the opening **30**, an upper portion of the dielectric material **38** may have the width **W1**, which is greater than the width **W2** of a lower portion of the dielectric material **38**. The widened opening **30** allows the dielectric material **38** to be filled with fewer defects (e.g., voids). Widening the opening **30** further results in the gate spacers (e.g., the gate seal spacer **80** and/or the gate spacers **86**) being thinner on the upper portion of the dielectric material **38** than on the lower portion of the dielectric material **38**. For example, the gate spacers have an upper portion that is thinner than a lower portion of the gate spacers. Further, by reducing etching of the dummy gate **72** along a bottom portion of the opening **30**, an effective gate width of the dummy gate **72** (and the subsequently formed replacement gate) can be maintained.

(76) FIGS. **20C** and **20D** illustrate top down views of the dielectric material **38**. FIG. **20C** illustrates a top down view taken along line X-X of FIG. **20B**, and FIG. **20D** illustrates a top down view taken along line Y-Y of FIG. **20B**. As illustrated by FIGS. **20C** and **20D**, an upper region of the dielectric material **38** is wider than a lower region of the dielectric material **38**. Further, in FIG. **20C**, the upper region of the dielectric material **38** may extend past first sidewalls of the gate spacers **80/86** towards second sidewalls of the gate spacers **80/86**. The first sidewalls may adjoin the dummy gate **72**, and the second sidewalls are opposite respective ones of the first sidewalls. In the upper region, the dielectric material **38** has the width **W1**, which is greater than a dimension **CD1** of the dummy gate **72**. The dimension **CD1** may be a distance between opposing sidewalls of the dummy gate **72** measured along a channel length direction of the dummy gate **72**. The width **W1** of the dielectric material **38** may further be less than a dimension **CD2** of the gate spacers **80/86**. The dimension **CD2** may be a distance between opposing outer sidewalls (e.g., the second sidewalls) of the gate spacers **80/86**. In FIG. **30D**, the dielectric material **38** may be bounded by the

first sidewalls of the gate spacers **80/86**. For example, the dielectric material **38** has a width **W2** in the lower region illustrated by FIG. **30D**, and the width **W2** may be equal to the dimension **CD1** of the dummy gate **72**. The width **W2** may also be less than the dimension **CD2** of the gate spacers **80/86**.

(77) FIGS. **22A** through **22E** illustrates an alternate configuration of the dielectric material **38**, which may be applied to either the device **10** (see FIGS. **20A** and **20B**) or the device **20** (see FIGS. **21A** and **21B**). FIG. **22A** illustrates a cross-sectional view of dielectric layer **38** having regions **38A**, **38B**, **38C**, and **38D**. FIGS. **22B**, **22C**, **22D**, and **22E** illustrate respective top down views of each of the regions **38A**, **38B**, **38C**, and **38D**. Each of the regions **38A**, **38B**, **38C**, and **38D** have a different width, which decreases in a direction towards the semiconductor substrate **50** (see FIGS. **20A** and **21A**). For example, the region **38A** has a width **W3**, which is greater than a width **W4** of the region **38B**. The width **W3** may further be greater than a dimension **CD3** of the dummy gate **72** and greater than a dimension **CD4** of the gate spacers **80/86**. In FIGS. **22B** through **22E**, the dimension **CD3** may be a distance between opposing sidewalls of the dummy gate **72** measured along a channel length direction of the dummy gate **72**, and the dimension **CD4** may be a distance between opposing outer sidewalls (e.g., opposite the dummy gate **72**) of the gate spacers **80/86**. The width **W4** of the region **38B** is greater than a width **W5** of the region **38C**. The width **W4** may further be greater than the dimension **CD3** of the dummy gate **72** and equal to the dimension **CD4** of the gate spacers **80/86**. The width **W5** of the region **38C** is greater than a width **W7** of the region **38D**. The width **W5** may be less than the dimension **CD4** of the gate spacers **80/86** and greater than the dimension **CD4** of the dummy gate **72**. The width **W6** may be equal to the dimension **CD3** of the dummy gate **72** and less than the dimension **CD4** of the gate spacers **80/86**.

(78) The configuration of FIGS. **22A** through **22E** may result from applying multiple cycles of the process described above with respect to FIGS. **18A** through **19B**. For example, FIGS. **22A** through **22E** may be achieved by applying three cycles. Further, by applying multiple cycles, an upper portion of the gate spacers **80/86** may be removed completely such that sidewalls of the dielectric material **38** directly contacts the first ILD **88**. Additional cycles or fewer cycles may be applied in other embodiments. For example, in other embodiments, one or more of the regions **38A** or **38B** may be omitted, or the dielectric material **38** may comprise one or more additional regions (e.g., wider regions) over the region **38A**.

(79) FIGS. **23A** through **23C** illustrate cross-sectional views of additional embodiments of the dielectric material **38**. Compared to the embodiments of FIGS. **20A** through **22E**, which illustrate the dielectric material **38** as having substantially (e.g., within manufacturing tolerances) straight sidewalls that are substantially perpendicular to a major surface of the semiconductor substrate **50**, the dielectric material **38** may also have sloped sidewalls. FIG. **23A** illustrates an embodiment where the dielectric material **38** has a continuously and constantly decreasing width in a direction towards the semiconductor substrate **50**. FIG. **23B** illustrates an embodiment where the dielectric material **38** has a continuously and discretely decreasing width in a direction towards the semiconductor substrate **50**. For example, in FIG. **23B**, a width of the dielectric material **38** may decrease abruptly at discrete intervals. FIG. **23C** illustrates an embodiment where the dielectric material **38** has both straight and sloped sidewall, and the gate spacers **80/86** only extend partially along sidewalls of the dielectric material **38**. A portion of the dielectric material **38** bounded by the gate spacers **80/86** may have a continuously and constantly decreasing width in a direction towards the semiconductor substrate **50** whereas a portion of the dielectric material **38** above the gate spacers **80/86** may have a substantially constant width (e.g., within manufacturing tolerances).

(80) FIGS. **24A** through **32B** illustrate additional immediate stages of forming a replacement gate and contacts to the transistor device. In FIGS. **24A** through **32B**, figures that end in "A" are illustrated along the respective cross-section A-A of FIGS. **1A** and **1B**, and Figures that end in "B" are illustrated along the respective cross-section B-B of FIGS. **1A** and **1B**.

(81) In FIGS. **24A** and **24B**, the remaining dummy gates **72**, and the masks **74** if present, are

removed in an etching step(s), so that recesses **90** are formed. Portions of the dummy dielectric layer **60** in the recesses **90** may also be removed. In some embodiments, only the dummy gates **72** are removed and the dummy dielectric layer **60** remains and is exposed by the recesses **90**. In some embodiments, the dummy dielectric layer **60** is removed from recesses **90** in a first region of a die (e.g., a core logic region) and remains in recesses **90** in a second region of the die (e.g., an input/output region). In some embodiments, the dummy gates **72** are removed by an anisotropic dry etch process. For example, the etching process may include a dry etch process using reaction gas(es) that selectively etch the dummy gates **72** without etching the first ILD **88** or the gate spacers **86**. Each recess **90** exposes and/or overlies a channel region **58** of a respective fin **52A**. Each channel region **58** is disposed between neighboring pairs of the epitaxial source/drain regions **82**. During the removal, the dummy dielectric layer **60** may be used as an etch stop layer when the dummy gates **72** are etched.

(82) The dummy dielectric layer **60** may then be optionally removed after the removal of the dummy gates **72**. In some embodiments, the dummy dielectric layer **60** may have a same material composition or a similar material composition as the passivation regions **34**. Accordingly, removing the dummy dielectric layer **60** may also remove a portion of the passivation regions **34** or completely remove the passivation regions **34** (e.g., as illustrated by FIGS. **25A** and **25B**).

(83) In FIGS. **26A** and **26B**, gate dielectric layers **92** and gate electrodes **94** are formed for replacement gates. FIG. **26C** illustrates a detailed view of region **89** of FIG. **26B**. FIG. **27** illustrates forming the gate dielectric layers **92** and the gate electrodes **94** in embodiments where the passivation regions **35** are removed. Gate dielectric layers **92** are deposited conformally in the recesses **90**, such as on the top surfaces and the sidewalls of the fins **52A**, on sidewalls of the dummy fin **52'**, on sidewalls of the dielectric material **38**, on sidewalls of the passivation regions **34** (if present) and on sidewalls of the gate seal spacers **80**/gate spacers **86**. The gate dielectric layers **92** may also be formed on the top surface of the first ILD **88**. In accordance with some embodiments, the gate dielectric layers **92** comprise silicon oxide, silicon nitride, or multilayers thereof. In some embodiments, the gate dielectric layers **92** include a high-k dielectric material, and in these embodiments, the gate dielectric layers **92** may have a k value greater than about 7.0, and may include a metal oxide or a silicate of hafnium, aluminum, zirconium, lanthanum, manganese, barium, titanium, lead, and combinations thereof. The formation methods of the gate dielectric layers **92** may include Molecular-Beam Deposition (MBD), ALD, PECVD, and the like. In embodiments where portions of the dummy gate dielectric **60** remains in the recesses **90**, the gate dielectric layers **92** include a material of the dummy gate dielectric **60** (e.g., SiO₂).

(84) The gate electrodes **94** are deposited over the gate dielectric layers **92**, respectively, and fill the remaining portions of the recesses **90**. By removing portions of the film **106** from sidewalls of the dummy fin **52'**, a space between the fins **52** and the dummy fin **52'** can be increased. As a result, the gate electrodes **94** can be deposited in the space around and between the fins **52**/dummy fin **52'** with fewer defects (e.g., fewer voids).

(85) The gate electrodes **94** may include a metal-containing material such as titanium nitride, titanium oxide, tantalum nitride, tantalum carbide, cobalt, ruthenium, aluminum, tungsten, combinations thereof, or multi-layers thereof. For example, although a single layer gate electrode **94** is illustrated in FIG. **26B**, the gate electrode **94** may comprise any number of liner layers **94A**, any number of work function tuning layers **94B**, and a fill material **94C** as illustrated by FIG. **26C**. After the filling of the recesses **90**, a planarization process, such as a CMP, may be performed to remove the excess portions of the gate dielectric layers **92** and the material of the gate electrodes **94**, which excess portions are over the top surface of the ILD **88**. The remaining portions of material of the gate electrodes **94** and the gate dielectric layers **92** thus form replacement gates of the resulting FinFETs. The gate electrodes **94** and the gate dielectric layers **92** may be collectively referred to as a "gate stack." The gate and the gate stacks may extend along sidewalls of a channel region **58** of the fins **52A**. The dielectric material **38** and the dummy fin **52'** isolates adjacent gate

stacks (e.g., gate stack **92A/94A** and gate stack **92B/94B**) when the adjacent gate stacks correspond to different FinFETs. For example, the gate stack **92A/94A** is arranged and separated from the gate stack **92B/94B** in a channel width direction by the dielectric material **38** and the dummy fin **52'** (if present). The adjacent gate stacks may be separated and arranged along the channel width direction of the FinFETs.

(86) The formation of the gate dielectric layers **92** in the region **50N** and the region **50P** may occur simultaneously such that the gate dielectric layers **92** in each region are formed from the same materials, and the formation of the gate electrodes **94** may occur simultaneously such that the gate electrodes **94** in each region are formed from the same materials. In some embodiments, the gate dielectric layers **92** in each region may be formed by distinct processes, such that the gate dielectric layers **92** may be different materials, and/or the gate electrodes **94** in each region may be formed by distinct processes, such that the gate electrodes **94** may be different materials. Various masking steps may be used to mask and expose appropriate regions when using distinct processes.

(87) In FIGS. **28A** and **28B**, the gate stack (including a gate dielectric layer **92** and a corresponding overlying gate electrode **94**) is recessed, so that a recess is formed directly over the gate stack and between opposing portions of gate spacers **86**. The etching process may be selective such that the dielectric material **38** is not significantly etched. A gate mask **96** comprising one or more layers of dielectric material, such as silicon nitride, silicon oxynitride, or the like, is filled in the recess, followed by a planarization process to remove excess portions of the dielectric material extending over the first ILD **88**. The subsequently formed gate contacts **110** (FIGS. **29A** and **29B**) penetrate through the gate mask **96** to contact the top surface of the recessed gate electrode **94**. The dielectric material **38** may extend through the gate mask **96**.

(88) In FIGS. **29A** and **29B**, a second ILD **108** is deposited over the first ILD **88**. In some embodiment, the second ILD **108** is a flowable film formed by a flowable CVD method. In some embodiments, the second ILD **108** is formed of a dielectric material such as PSG, BSG, BPSG, USG, or the like, and may be deposited by any suitable method, such as CVD and PECVD.

(89) Also illustrated in FIGS. **29A** and **29B**, gate contacts **110** and source/drain contacts **112** are formed through the second ILD **108** and the first ILD **88** in accordance with some embodiments. FIGS. **30A** and **30B** illustrate an analogous step in embodiments where the passivation regions **34** are removed. FIGS. **31A** and **31B** illustrate an analogous stage of manufacturing in the device **20** where the dummy fin **52'** is omitted, and FIGS. **32A** and **32B** illustrate an analogous stage of manufacturing in the device **20** where the dummy fin **52'** is omitted and the passivation regions **34** are also removed. Openings for the source/drain contacts **112** are formed through the first and second ILDs **88** and **108**, and openings for the gate contact **110** are formed through the second ILD **108** and the gate mask **96**. The openings may be formed using acceptable photolithography and etching techniques. A liner, such as a diffusion barrier layer, an adhesion layer, or the like, and a conductive material are formed in the openings. The liner may include titanium, titanium nitride, tantalum, tantalum nitride, or the like. The conductive material may be copper, a copper alloy, silver, gold, tungsten, cobalt, aluminum, nickel, or the like. A planarization process, such as a CMP, may be performed to remove excess material from a surface of the ILD **108**. The remaining liner and conductive material form the source/drain contacts **112** and gate contacts **110** in the openings. An anneal process may be performed to form a silicide at the interface between the epitaxial source/drain regions **82** and the source/drain contacts **112**. The source/drain contacts **112** are physically and electrically coupled to the epitaxial source/drain regions **82**, and the gate contacts **110** are physically and electrically coupled to the gate electrodes **106**. The source/drain contacts **112** and gate contacts **110** may be formed in different processes, or may be formed in the same process. Although shown as being formed in the same cross-sections, it should be appreciated that each of the source/drain contacts **112** and gate contacts **110** may be formed in different cross-sections, which may avoid shorting of the contacts.

(90) The above embodiments describe the dielectric material **38** being formed prior to the gate

stacks **92/94**. In other embodiments, the gate stacks (e.g., comprising gate dielectric **92** and gate electrodes **94**) may be formed prior to forming the dielectric material **38**. For example, FIGS. **33A** through **36D** illustrate intermediate cross-sectional views of forming the dielectric material after the gate stacks **92/94** using a metal gate cut process, for example. In FIGS. **33A** through **36B**, figures that end in “A” are illustrated along the respective cross-section A-A of FIGS. **1A** and **1B**, and Figures that end in “B” are illustrated along the respective cross-section D-D of FIGS. **1A** and **1B**. FIGS. **36C** and **36D** illustrate top-down views. FIGS. **33A** through **36D** illustrate similar processes as those described above with respect to FIGS. **17A** through **20D** where like reference numerals indicate like elements formed using like processes.

(91) In FIGS. **33A** and **33B**, the gate stack **92/94** may be etched to define an opening (e.g., as described above with respect to FIGS. **17A** and **17B**). In embodiments with a dummy fin **52'**, the opening **30** may be formed directly over the dummy fin **52'**.

(92) One or more cycles of a treatment process (e.g., as described above with respect to FIGS. **18A** and **18B**) and an etching process (e.g., as described above with respect to FIGS. **19A** and **19B**) may be applied to the opening **30** until a dummy fin **52'** or an STI region **56** is exposed. FIGS. **34A** and **34B** illustrate the treatment process, and FIGS. **35A** and **35B** illustrate the etching process. As a result of the treatment process(s) of FIGS. **34A** and **34B**, passivation regions **40** may be formed in the gate electrodes **94**. The passivation regions **40** may comprise a material of the gate electrode **94** and an element used during the treatment process(s). For example, the passivation regions **40** may comprise a metal oxide, a metal nitride, or the like.

(93) In FIGS. **36A** and **36B**, a dielectric material **38** may then be deposited in the opening **30** (e.g., as described above with respect to FIGS. **20A** through **20D**). The dielectric material **38** and the dummy fin **52'** (if present) separate the gate stacks **92A/94A** and **92B/94B** of adjacent transistor devices. For example, the gate stack **92A/94A** is arranged and separated from the gate stack **92B/94B** in a channel width direction by the dielectric material **38** and the dummy fin **52'** (if present). The passivation regions **40** may have a uniform material composition throughout and be disposed on sidewalls of the dielectric material **38**. For example, the passivation regions **40** may separate portions of the dielectric material **38** from the gate electrode **94**. FIG. **36C** illustrates a top-down view of an upper portion of the dielectric material (e.g., taken along line X-X of FIG. **36B**), and FIG. **36D** illustrates a top-down view of a lower portion of the dielectric material **38** (e.g., taken along line Y-Y of FIG. **36B**). As illustrated, the upper portion of the dielectric material **38** may have a width **W1** that is wider than a width **W2** of the lower portion of the dielectric material **38**.

(94) Similar processes as described above with respect to FIGS. **28A** through **29B** may be applied to recess the gate stack **92/94**, form a gate mask layer **96** over the recessed gate stack **92/94**, and form contacts to the transistor. The resulting structure is illustrated in FIGS. **37A** and **37B**. FIGS. **38A** and **38B** illustrate an alternative embodiment where the dummy fin **52'** is excluded and the dielectric material **38** is formed after the gate stacks **92/94**.

(95) The disclosed FinFET embodiments could also be applied to nanostructure devices such as nanostructure (e.g., nanosheet, nanowire, gate-all-around, or the like) field effect transistors (NSFETs). In an NSFET embodiment, the fins are formed by patterning a stack of alternating layers of channel layers and sacrificial layers. Embodiments may include between two and ten channel layer/sacrificial layer pairs, for example. In some embodiments, a width of the stack may be in a range of about 30 Å to about 5000 Å, such as in a range of about 30 Å to about 3000 Å. The dummy gate stacks and source/drains are formed in a similar manner as described above. After the dummy gate stacks are removed, the sacrificial layers can be partially or fully removed in the channel regions. The replacement gate structures are formed in a similar manner as described above and will partially or completely surround the channel layers in the channel region of the NSFET devices. The ILDs and contacts to the gate structures and source/drains are formed in a similar manner as described above. A nanostructure device can be formed as disclosed in U.S.

(96) In various embodiments, a dielectric material may be used to separate metal gates of adjacent transistors. The dielectric material may be formed by patterning an opening in a dummy gate stack or a metal gate stack and filling the dielectric material in the opening. An upper portion of the opening may be widened, thereby improving a gap fill window of the dielectric material and reducing manufacturing defects. Further a lower portion of the opening may not be widened, and an effective gate width of the adjacent gate stacks may be maintained. In some embodiments, widening the upper portion of the opening may be achieved one or more cycles of treatment and etching processes. Accordingly, an atomic layer etch type process may be achieved to control effective gate width and enlarge the dielectric material gap fill window. Manufacturing defects can be reduced, and device performance can be improved.

(97) In some embodiments, a device includes a semiconductor substrate and a first gate stack over the semiconductor substrate, the first gate stack being between a first gate spacer and a second gate spacer. The device further includes a second gate stack over the semiconductor substrate between the first gate spacer and the second gate spacer and a dielectric material separating the first gate stack from the second gate stack. The dielectric material is at least partially between the first gate spacer and the second gate spacer, a first width of an upper portion of the dielectric material is greater than a second width of a lower portion of the dielectric material, and a third width of an upper portion of the first gate spacer is less than a fourth width of a lower portion of the first gate spacer. In some embodiments, a fifth width of an upper portion of the second gate spacer is less than a sixth width of a lower portion of the second gate spacer. In some embodiments, the device further comprises a passivation region between the upper portion of the dielectric material and the first gate stack. In some embodiments, the passivation region comprises a metal oxide or a metal nitride. In some embodiments, the device further includes a dummy fin under the dielectric material, the dummy fin separating the first gate stack from the second gate stack. In some embodiments, the dielectric material extends to and contacts a shallow trench isolation (STI) region. In some embodiments, the dielectric material has sloped sidewalls. In some embodiments, the dielectric material has straight sidewalls that are perpendicular to a major surface of the semiconductor substrate. In some embodiments, the upper portion of the dielectric material is above the first gate spacer and the second gate spacer. In some embodiments, the upper portion of the first gate spacer contacts a sidewall of the upper portion of the dielectric material. In some embodiments, the first width is greater than a distance between a first sidewall of the first gate stack and a second sidewall of the first gate stack, the distance is measured along a channel length direction of the first gate stack.

(98) In some embodiments, a device includes a first transistor at a top surface of a semiconductor substrate, the first transistor comprising: a first channel region; and a first gate stack over and along sidewalls of the first channel region; a second transistor at the top surface of the semiconductor substrate, the second transistor comprising: a second channel region; and a second gate stack over and along sidewalls of the second channel region; a dielectric material separating the first gate stack from the second gate stack in a channel width direction of the first transistor, the dielectric material comprising: a first portion having a first width; and a second portion over the first portion, the second portion having a second width greater than the first width; and a first passivation region between the second portion of the dielectric material and the first gate stack. In some embodiments, the device further includes a first gate spacer along first sidewalls of the first transistor, the second transistor, and the dielectric material; and a second gate spacer along second sidewalls of the first transistor, the second transistor, and the dielectric material. In some embodiments, the device further includes a dummy fin under and adjoining the dielectric material, the dummy fin separating the first gate stack from the second gate stack in the channel width direction of the first transistor.

(99) In some embodiments, a method includes etching an opening in a gate stack, the opening

exposing sidewalls of gate spacers, and the gate spacers being disposed on sidewalls of the gate stack; performing a treatment process in the opening, wherein the treatment process defines: a first passivation region in the sidewalls of the gate spacers; and a second passivation region in the gate stack; extending the opening through the gate stack using an etch process, the etching process removes the first passivation region; and after extending the opening through the gate stack, filling the opening with a dielectric material. In some embodiments, the gate stack comprises a metal gate electrode. In some embodiments, the gate stack is a dummy gate stack, and the method further comprises after filling the opening with the dielectric material, replacing the gate stack with a second gate stack. In some embodiments, extending the opening through the gate stack comprises exposing a dummy fin. In some embodiments, the etching process is a directional etch process. In some embodiments, the etching process is a selective etch that removes the first passivation region at a greater rate than the second passivation region.

(100) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A device comprising: a semiconductor substrate; a first gate stack over the semiconductor substrate; a second gate stack over the semiconductor substrate; an isolation structure between and contacting the first gate stack and the second gate stack, a first width of an upper portion of the isolation structure is greater than a second width of a lower portion of the isolation structure, the first width and the second width each being measured along a first cross-section perpendicular to a lengthwise dimension of the first gate stack, the first width being measured at a topmost surface of the isolation structure in the first cross-section, and the second width being measured at a bottommost surface of the isolation structure in the first cross-section; and a first gate spacer on a first sidewall of the isolation structure, wherein a third width of a first upper portion of the first gate spacer is less than a fourth width of a first lower portion of the first gate spacer, the third width and the first width are each being measured along the first cross-section.
2. The device of claim 1, wherein the first upper portion of the first gate spacer contacts the isolation structure, wherein a second upper portion of the first gate spacer contacts the first gate stack, and wherein a fifth width of the second upper portion of the first gate spacer is greater than the third width, the fifth width being measured along a second cross-section perpendicular to the lengthwise dimension of the first gate stack and parallel to the first cross-section.
3. The device of claim 2, wherein the first lower portion of the first gate spacer contacts the isolation structure, wherein a second lower portion of the first gate spacer contacts the first gate stack, and wherein a sixth width of the second lower portion of the first gate spacer is equal to the fourth width, the sixth width being measured along the second cross-section.
4. The device of claim 3, wherein the fifth width is equal to the sixth width.
5. The device of claim 1, wherein the isolation structure comprises: a dielectric material contacting the first gate stack and the second gate stack.
6. The device of claim 5, wherein the isolation structure further comprises a passivation material between a sidewall of the dielectric material and the first gate stack.
7. The device of claim 5, wherein the dielectric material extends to a top surface of a shallow trench isolation (STI) region.

8. The device of claim 5, wherein the isolation structure further comprises: a dummy fin, wherein the dielectric material extends to a top surface of the dummy fin.
 9. A device comprising: a first transistor at a top surface of a semiconductor substrate, the first transistor comprising a first gate stack; a second transistor at the top surface of the semiconductor substrate, the second transistor comprising a second gate stack; a dielectric material separating the first gate stack from the second gate stack in a channel width direction of the first transistor, the dielectric material comprising: a first portion having a first width measured in the channel width direction; and a second portion over the first portion, the second portion having a second width greater than the first width, the second width being measured in the channel width direction; a first passivation region between the second portion of the dielectric material that has the second width and the first gate stack; and a gate spacer on a sidewall of the dielectric material, wherein an upper portion of the gate spacer has a third width less than a fourth width of a lower portion of the gate spacer.
 10. The device of claim 9, wherein the upper portion of the gate spacer is in physical contact with the second portion of the dielectric material, and the lower portion of the gate spacer is in physical contact with the first portion of the dielectric material.
 11. The device of claim 9, wherein the first passivation region separates the second portion of the dielectric material from the first gate stack in the channel width direction of the first transistor, and the gate spacer is disposed in a cross-sectional view that is perpendicular to the channel width direction.
 12. The device of claim 9 further comprising a second passivation region between the second portion of the dielectric material and the second gate stack.
 13. The device of claim 9, wherein the first passivation region comprises oxygen or nitrogen.
 14. The device of claim 13, wherein the first passivation region further comprises silicon.
 15. The device of claim 13, wherein a gate electrode of the first gate stack comprises a metal, the first passivation region further comprises the metal.
 16. A device comprising: a semiconductor substrate; first and second gate spacers on the semiconductor substrate, wherein a top surface of the first gate spacer is narrower than a bottom surface of the first gate spacer; a first gate stack between the first and second gate spacers; a second gate stack between the first and second gate spacers; and a dielectric material isolating the first gate stack from the second gate stack, the dielectric material being further disposed between the first gate spacer and the second gate spacer, a top surface of the dielectric material being wider than a bottom surface of the dielectric material.
 17. The device of claim 16, wherein the dielectric material contacts the first gate stack and the second gate stack at the top surface of the dielectric material.
 18. The device of claim 16 further comprising a passivation region between the dielectric material and the first gate stack.
 19. The device of claim 16, wherein the dielectric material extends to a top surface of a shallow trench isolation (STI) region.
 20. The device of claim 16 further comprising a dummy fin on a top surface of the semiconductor substrate, wherein the dielectric material extends to a top surface of the dummy fin.
-