

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12400680
Kind Code	B1
Date of Patent	August 26, 2025
Inventor(s)	Le; Quang et al.

Head and media overcoats for heat assisted magnetic recording

Abstract

The present disclosure generally relates to a magnetic recording drive comprising a write head disposed over a media. The write head comprises a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS) and a head overcoat disposed on the MFS, the head overcoat comprising SiN. The head overcoat has an extinction coefficient (k) value of about 0.0. The media comprises a media overcoat disposed adjacent to the head overcoat. The media overcoat comprises a first layer of C and a second layer of SiN disposed on the first layer. The media overcoat has a k-value of about 0.5 or greater. The head overcoat is transparent while the media overcoat is heat absorbent.

Inventors: Le; Quang (San Jose, CA), Trinh; Tan Duy (San Jose, CA), Osman; Hassan (San Jose, CA), Maeda; Maki (Fujisawa, JP), Dai; Qing (San Jose, CA), Takano; Hisashi (Fujisawa, JP)

Applicant: Western Digital Technologies, Inc. (San Jose, CA)

Family ID: 1000007870423

Assignee: Western Digital Technologies, Inc. (San Jose, CA)

Appl. No.: 18/652371

Filed: May 01, 2024

Publication Classification

Int. Cl.: G11B20/10 (20060101); G11B5/31 (20060101); G11B5/72 (20060101); G11B5/84 (20060101); G11B13/08 (20060101); G11B5/00 (20060101)

U.S. Cl.:

CPC **G11B5/7264** (20200801); **G11B5/84** (20130101); **G11B13/08** (20130101);
G11B2005/0021 (20130101)

Field of Classification Search

CPC: G11B (5/738); G11B (5/40); G11B (5/645); G11B (5/653); G11B (5/732); G11B
(2005/0021); G11B (5/41); G11B (5/3106); G11B (5/62); G11B (5/65); G11B (5/855);
G11B (11/10584); G11B (11/10586); G11B (7/716); G11B (5/714); G11B (5/4826);
G11B (5/4866)

USPC: 360/59

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5942317	12/1998	White	N/A	N/A
6537686	12/2002	Chen	N/A	N/A
6565719	12/2002	Lairson et al.	N/A	N/A
6576328	12/2002	Deng et al.	N/A	N/A
6583953	12/2002	Han et al.	N/A	N/A
7286326	12/2006	Yasui et al.	N/A	N/A
7782569	12/2009	Cheng et al.	N/A	N/A
8014104	12/2010	Cheng et al.	N/A	N/A
8472134	12/2012	Kodama et al.	N/A	N/A
8559136	12/2012	Matsumura et al.	N/A	N/A
8638645	12/2013	Nishijima et al.	N/A	N/A
8687323	12/2013	Marchon et al.	N/A	N/A
8721903	12/2013	Bian et al.	N/A	N/A
8902720	12/2013	Schreck et al.	N/A	N/A
9036307	12/2014	Hoshiya et al.	N/A	N/A
9460738	12/2015	Torres et al.	N/A	N/A
9530445	12/2015	Grobis	N/A	G11B 5/658
9940953	12/2017	Zavaliche et al.	N/A	N/A
10121506	12/2017	Xu et al.	N/A	N/A
10643648	12/2019	Zhang et al.	N/A	N/A
10796719	12/2019	Jubert et al.	N/A	N/A
11074929	12/2020	Herber	N/A	G11B 5/255
11127421	12/2020	Siangchaew et al.	N/A	N/A
11348603	12/2021	Bergerud et al.	N/A	N/A
12159654	12/2023	Habibollahzadeh et al.	N/A	N/A
2006/0286292	12/2005	Jiang et al.	N/A	N/A
2008/0187781	12/2007	Cheng et al.	N/A	N/A
2011/0032640	12/2010	Marchon et al.	N/A	N/A
2013/0114165	12/2012	Mosendz	360/244	G11B 5/7264
2021/0118469	12/2020	Khamnualthong et al.	N/A	N/A
2023/0238023	12/2022	Trinh et al.	N/A	N/A

Background/Summary

BACKGROUND OF THE DISCLOSURE

Field of the Disclosure

(1) Embodiments of the present disclosure generally relate to a magnetic media drive comprising a magnetic recording head and a media.

Description of the Related Art

(2) The heart of the functioning and capability of a computer is the storing and writing of data to a data storage device, such as a magnetic media drive (e.g., hard disk drive (HDD)). The volume of data processed by a computer is increasing rapidly. There is a need for higher recording density of a magnetic recording medium to increase the function and the capability of a computer.

(3) In order to achieve higher recording densities, such as recording densities exceeding 2 Tbit/in.² for a magnetic recording medium, the width and pitch of write tracks are narrowed, and thus the corresponding magnetically recorded bits encoded in each write track is narrowed. One challenge in narrowing the width and pitch of write tracks is decreasing a surface area of a main pole of the magnetic recording write head at a media facing surface (MFS). As the main pole becomes smaller, the recording field becomes smaller as well, limiting the effectiveness of the magnetic recording write head.

(4) Heat-assisted magnetic recording (HAMR) and microwave assisted magnetic recording (MAMR) are two types of energy-assisted magnetic recording (EAMR) technology to improve the recording density of a magnetic recording medium. In HAMR, a laser source is located next to or near the write element of the magnetic recording write head in order to produce heat, such as a laser source exciting a near-field transducer (NFT) to produce heat at a write location of a magnetic recording medium. Gold is typically used for the NFT material to achieve a high optical efficiency, but the melting point of gold is low and deformation of the NFT is a problem when the NFT is heated for a long term. The NFT temperature is especially high near the point where the optical near-field is generated, and the maximum temperature may reach more than 150 degrees Celsius over the operational temperature of the magnetic disk device, causing the NFT to deform.

(5) Therefore, there is a need in the art for an improved HAMR magnetic media drive.

SUMMARY OF THE DISCLOSURE

(6) The present disclosure generally relates to a magnetic recording drive comprising a write head disposed over a media. The write head comprises a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS) and a head overcoat disposed on the MFS, the head overcoat comprising SiN. The head overcoat has an extinction coefficient (k) value of about 0.0. The media comprises a media overcoat disposed adjacent to the head overcoat. The media overcoat comprises a first layer of C and a second layer of SiN disposed on the first layer. The media overcoat has a k-value of about 0.5 or greater. The head overcoat is transparent while the media overcoat is heat absorbent.

(7) In one embodiment, a magnetic recording drive comprises a write head, the write head comprising a head overcoat disposed on a media facing surface (MFS), the head overcoat comprising SiN, and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a first layer of SiN disposed over a second layer of C.

(8) In another embodiment, a magnetic recording drive comprises a write head, the write head

comprising: a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS), and a head overcoat disposed on the MFS, the head overcoat comprising SiN, and a head overcoat disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having an extinction coefficient (k) value of about 0.0, and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a bilayer of SiN and C, with the C layer having a k-value of 0.5 or greater.

(9) In yet another embodiment, a magnetic recording drive comprises a write head, the write head comprising: a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS), and a transparent head overcoat disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having a heat extinction coefficient (k) value of less than about 0.1, and a media disposed adjacent to the MFS of the write head, the media comprising an absorbent media overcoat comprising a first layer of C and a second layer SiN, the first layer of C having a k-value of 0.5 or greater.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) So that the manner in which the above recited features of the present disclosure can be understood in detail, a more particular description of the disclosure, briefly summarized above, may be had by reference to embodiments, some of which are illustrated in the appended drawings. It is to be noted, however, that the appended drawings illustrate only typical embodiments of this disclosure and are therefore not to be considered limiting of its scope, for the disclosure may admit to other equally effective embodiments.

(2) FIG. 1 is a schematic illustration of certain embodiments of a magnetic media drive including a HAMR magnetic write head.

(3) FIG. 2 is a schematic illustration of certain embodiments of a cross sectional side view of a HAMR write head facing a magnetic disk.

(4) FIG. 3 illustrates a cross-sectional MFS view of a HAMR write head disposed over a media, according to one embodiment.

(5) FIG. 4A illustrates the media overcoat (MOC) of FIG. 3, according to one embodiment.

(6) FIG. 4B illustrates the head overcoat (HOC) of FIG. 3, according to one embodiment.

(7) FIG. 5 illustrates a deposition process for forming the SiN layer having a low k-value of about 0.0 for the HOC and the MOC, according to one embodiment.

(8) FIG. 6 illustrates a graph 600 showing the k-value of the carbon layer versus deposition temperature (° C.) when forming the carbon layer, according to one embodiment.

(9) To facilitate understanding, identical reference numerals have been used, where possible, to designate identical elements that are common to the figures. It is contemplated that elements disclosed in one embodiment may be beneficially utilized on other embodiments without specific recitation.

DETAILED DESCRIPTION

(10) In the following, reference is made to embodiments of the disclosure. However, it should be understood that the disclosure is not limited to specific described embodiments. Instead, any combination of the following features and elements, whether related to different embodiments or not, is contemplated to implement and practice the disclosure. Furthermore, although embodiments of the disclosure may achieve advantages over other possible solutions and/or over the prior art, whether or not a particular advantage is achieved by a given embodiment is not limiting of the disclosure. Thus, the following aspects, features, embodiments and advantages are merely

illustrative and are not considered elements or limitations of the appended claims except where explicitly recited in a claim(s). Likewise, reference to “the disclosure” shall not be construed as a generalization of any inventive subject matter disclosed herein and shall not be considered to be an element or limitation of the appended claims except where explicitly recited in a claim(s).

(11) The present disclosure generally relates to a magnetic recording drive comprising a write head disposed over a media. The write head comprises a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS) and a head overcoat disposed on the MFS, the head overcoat comprising SiN. The head overcoat has an extinction coefficient (k) value of about 0.0. The media comprises a media overcoat disposed adjacent to the head overcoat. The media overcoat comprises a first layer of C and a second layer of SiN disposed on the first layer. The media overcoat has a k -value of about 0.5 or greater. The head overcoat is transparent while the media overcoat is heat absorbent.

(12) FIG. 1 is a schematic illustration of certain embodiments of a magnetic media drive **100** including an energy-assisted magnetic recording (EAMR) write head, such as a heat-assisted magnetic recording (HAMR) or microwave assisted magnetic recording (MAMR) write head. Such magnetic media drive may be a single drive/device or comprise multiple drives/devices. For the ease of illustration, a single disk drive **100** is shown according to one embodiment. The disk drive **100** includes at least one rotatable magnetic recording medium **112** (oftentimes referred to as magnetic disk **112**) supported on a spindle **114** and rotated by a drive motor **118**. The magnetic recording on each magnetic disk **112** is in the form of any suitable patterns of data tracks, such as annular patterns of concentric data tracks (not shown) on the magnetic disk **112**.

(13) At least one slider **113** is positioned near the magnetic disk **112**. Each slider **113** supports a head assembly **121** including one or more read heads and one or more write heads such as a HAMR write head. As the magnetic disk **112** rotates, the slider **113** moves radially in and out over the disk surface **122** so that the head assembly **121** may access different tracks of the magnetic disk **112** where desired data are written. Each slider **113** is attached to an actuator arm **119** by way of a suspension **115**. The suspension **115** provides a slight spring force which biases the slider **113** toward the disk surface **122**. Each actuator arm **119** is attached to an actuator **127**. The actuator **127** as shown in FIG. 1 may be a voice coil motor (VCM). The VCM includes a coil movable within a fixed magnetic field, the direction and speed of the coil movements being controlled by the motor current signals supplied by control unit **129**.

(14) During operation of the disk drive **100**, the rotation of the magnetic disk **112** generates an air bearing between the slider **113** and the disk surface **122** which exerts an upward force or lift on the slider **113**. The air bearing thus counter-balances the slight spring force of suspension **115** and supports slider **113** off and slightly above the disk surface **122** by a small, substantially constant spacing during normal operation.

(15) The various components of the disk drive **100** are controlled in operation by control signals generated by control unit **129**, such as access control signals and internal clock signals. Typically, the control unit **129** comprises logic control circuits, storage means, and a microprocessor. The control unit **129** generates control signals to control various system operations such as drive motor control signals on line **123** and head position and seek control signals on line **128**. The control signals on line **128** provide the desired current profiles to optimally move and position slider **113** to the desired data track on magnetic disk **112**. Write and read signals are communicated to and from the head assembly **121** by way of recording channel **125**. Certain embodiments of a magnetic media drive of FIG. 1 may further include a plurality of media, or disks, a plurality of actuators, and/or a plurality number of sliders.

(16) FIG. 2 is a schematic illustration of certain embodiments of a cross sectional side view of a HAMR write head **230** facing a magnetic disk **112**. The HAMR write head **230** may correspond to part of the reading/recording head assembly **121** described in FIG. 1 or a recording head used in

other magnetic media drives. The HAMR write head **230** includes a media facing surface (MFS), such as an air bearing surface (ABS) or a gas bearing surface (GBS), facing the disk **112**. As shown in FIG. 2, the magnetic disk **112** and the HAMR write head **230** relatively moves in the direction indicated by the arrows **282** (need to change direction).

(17) The HAMR write head **230** includes a main pole **236** disposed between a leading return shield **234** and a trailing return shield **238**. The main pole **236** can include a main pole tip **237** at the MFS. The main pole tip **237** can include or not include a leading taper and/or a trailing taper. A coil **260** around the main pole **236** excites the main pole tip **237** to produce a writing magnetic field for affecting a magnetic medium of the rotatable magnetic disk **112**. The coil **260** may be a helical structure or one or more sets of pancake structures. The leading return shield **234** and/or the trailing return shield **238** can act as the return pole for the main pole **236**.

(18) The magnetic disk **112** is positioned adjacent to or under the HAMR write head **230**. A magnetic field produced by current in the coil **260** is used to control the direction of magnetization of bits in the magnetic disk **112**.

(19) The HAMR write head **230** includes a structure for heating the magnetic disk **112** proximate to where the main pole tip **237** applies the magnetic write field to the storage media. A waveguide **242** is positioned between the main pole **236** and the leading return shield **234**. The waveguide **242** can include a core layer and a cladding layer surrounding the core layer. The waveguide **242** conducts light from a light source **278** of electromagnetic radiation, which may be, for example, ultraviolet, infrared, or visible light. The light source **278** may be, for example, an edge emitting laser diode (EELD) or a vertical cavity surface emitting laser (VCSEL) device, a laser diode, or other suitable laser light source for directing a light beam toward the waveguide **242**. Various techniques that are known for coupling the light source **278** into the waveguide **242** may be used. For example, the light source **278** may work in combination with an optical fiber and external optics for directing a light beam to the waveguide **242**. Alternatively, the light source **278** may be mounted on the waveguide **242** and the light beam may be directly coupled into the waveguide **242** without the need for external optical configurations. Once the light beam is coupled into the waveguide **242**, the light propagates through the waveguide and heats a portion of the media, as the media moves relative to the HAMR write head **230** as shown by arrows **282**.

(20) The HAMR write head **230** can include a near-field transducer (NFT) **284** to concentrate the heat in the vicinity of the end of the waveguide **242**. The NFT **284** is positioned in or adjacent to the waveguide **242** near or at the MFS. Light from the waveguide **242** is absorbed by the NFT **284** and excites surface plasmons which travel along the outside of the NFT **284** towards the MFS concentrating electric charge at the tip of the NFT **284** which in turn capacitively couples to the magnetic disk and heats a precise area of the magnetic disk **112** by Joule heating. One possible NFT **284** for the HAMR write head is a lollipop design with a disk portion and a peg extending between the disk and the MFS. The NFT **284** can be placed in close proximity to the main pole **236**. The NFT **284** is relatively thermally isolated and absorbs a significant portion of the laser power while it is in resonance.

(21) The waveguide **242**, may be a spot size converter (SSC) that includes numerous waveguides and a multimodal interference (MMI) device. The present disclosure generally relates to the management and enhancement of the profile of the SSC. The SSC discussed herein results in significant improvement in the overall coupling efficiency between a coherent light source and the waveguide inside a photonic integrated circuit (PIC) or planar waveguide circuit (PLC) of a HAMR head slider. The geometry and position of the core materials/assist core channels both on the lateral and vertical vicinity of a center waveguide core are discussed herein. The overall field profile of the SSC can be tuned to match the field profile or the mode of a coherent light source, leading to significant enhancement in the overall coupling efficiency. The waveguide **242** or SSC may comprise a material selected from the group consisting of: Ta.sub.2O.sub.5, Nb.sub.2O.sub.3, TiO.sub.2, Y.sub.2O.sub.3, SiN, SiC, and AlN, where the refracting index of core must be lower

than that of cladding.

(22) Optical power from an external coherent light source (i.e., EELD, surface emitting diode laser, VCSEL device, or fiber coupled diode laser) is coupled into the PLC of the HAMR head slider through the SSC or mode converter. The basic design concept is to match the mode profile of the incoming light source and the mode profile of the PLC, both at the coupling interface, hence maximizing the overall coupling efficiency.

(23) FIG. 3 illustrates a cross-sectional MFS view of a HAMR write head **300** disposed over a media **313**, according to one embodiment. The HAMR write head **300** may be a part of the magnetic media drive **100** of FIG. 1. The HAMR write head may be the HAMR write head **230** of FIG. 2.

(24) The HAMR write head **300** comprises a NFT **302**. Adhesion layers **318** are disposed adjacent to the NFT **302**, and cladding material **316** is disposed adjacent to the adhesion layers **318**. A head overcoat (HOC) **304** covers the MFS of the HAMR write head **300**. The media **313** comprises a magnetic recording layer **314**, a capping layer **312** disposed on the magnetic recording layer **314**, a media overcoat (MOC) **310** disposed on the capping layer **312**, and a lubricant **308** disposed on MOC **310**. The capping layer **312** may comprise a magnetic material or a magnetic stack of materials, such as Co, Ni, Fe, Pt, and combinations thereof, have a high extinction coefficients (k) value, such as about 0.5 or greater, and a thickness of about 1 nm to about 5 nm. The lubricant may comprise a backbone structure and functional groups that bonds to the carbon overcoat on the media **313** and have a thickness of about 0.5 nm to about 5 nm.

(25) During operation, a smear **306** may be formed from contamination and/or mixing of the lubricant **308**, the MOC **310**, and the HOC **304**, which may then be transferred to the surface of the HAMR write head **300** via evaporation/condensation due to a temperature difference between the head and media surfaces. The smear **306** may be formed due to the HOC **304** and the MOC **310** having non-optimal k -value. For example, the MOC **310** typically has a k -value of about 0.058, and the HOC **304** typically has a k -value of about 0.2, causing the HOC **304** to be non-transparent and the MOC **310** to be non-absorbing. The non-optimal k -values further result in the smear **306** having a k -value of about 0.075, indicating significant optical power loss. The smear **306** may cause the head flying height to increase, causing reliability issues in the head **300**. If the smear **306** in the vicinity of the NFT **302** is not removed, it can lead to temperature rising in the vicinity of the NFT **302** and failure of the NFT **302** eventually. Note that in practice there may be a clearance between the head **300** and media **313** in the space occupied by smear **306** in this figure, but it is not shown here for simplicity of illustrative purposes.

(26) However, properties of the MOC **310** and the HOC **304** can be selected to eliminate the negative aspects of the smear **306**. As described herein, a MOC **310** comprising a bilayer of carbon having a high k -value and SiN having a low k -value, and a HOC **304** comprising SiN having a low k -value, results in the HOC **304** being transparent and the MOC **310** being heat absorbing, eliminates negative impacts from the smear **306**, as the smear **306** will be transparent. The transparent HOC **304** and the absorbing MOC **310** increases the absorption in the media **313** and reduces the laser power in the head **300**, reducing the temperature difference between the head and media surfaces, thus improving the reliability of the NFT **302**.

(27) FIG. 4A illustrates the MOC **310** of FIG. 3, according to one embodiment. FIG. 4B illustrates the HOC **304** of FIG. 3, according to one embodiment. The MOC **310** comprises a bilayer, the bilayer comprising a first layer **418** of carbon having a high k -value of about 0.5 or greater and a second layer **420** of SiN having a low k -value of less than about 0.1, such as about 0.0. The SiN layer **420** is disposed on the carbon layer **418** such that the smear **306** will be disposed on the SiN layer **420**. The carbon layer **418** has a thickness of about 2 nm to about 4 nm, and the SiN layer **420** of the MOC **310** has a thickness of about 0.4 nm to about 1 nm. The HOC **304** comprises SiN **420** having a low k -value of less than about 0.1, such as about 0.0. The SiN layer **420** of the HOC **304** has a thickness of about 1 nm to about 4 nm. Such optimal k -values result in any smear **306** having

a k-value of less than about 0.1, such as 0.0, preventing optical power loss.

(28) Because the SiN layer **420** of the MOC **310** is disposed on top of the carbon layer **418**, a smear **306** will be disposed between the SiN layer **420** of the MOC **310** and the SiN layer of the HOC **304**. As such, the smear **306** will comprise SiN having a low k-value of less than about 0.1, such as about 0.0 as well, resulting in the smear **306** being transparent. In other words, the smear **306** is comprised of a portion of the SiN layer **420** of the HOC **304** and a portion of the SiN layer **420** of the MOC **310**.

(29) FIG. 5 illustrates a deposition process for forming the SiN layer **420** having a low k-value of about 0.0 for the HOC **304** and the MOC **310**, according to one embodiment. The HOC **304** is formed in a chamber **528**, such as an atomic layer deposition (ALD) chamber or a plasma enhanced (PE) ALD chamber. The chamber **528** is first cleaned to eliminate any debris. Forming the SiN layer **420** comprises two half-cycle reactions within the chamber **528**. In the first half-cycle reaction, a substrate **526** within the chamber **528** is exposed to silicon **522**, and chemisorption interactions allow precursor molecules of silicon **522** to “stick” to the surface of the substrate **526**. The chamber **528** is then purged.

(30) During the second half-cycle reaction, the substrate **526** having the silicon **522** disposed thereon is exposed to nitrogen **524**, which serves the purpose of eliminating the undesired surface components and forming the silicon-nitrogen bonds. The silicon **522** surface provides reactive sites for the nitrogen adsorption to form the silicon-nitrogen bonds, where nitrogen **524** is on the top surface of the SiN layer **420** to improve adhesion to the lubricant **308**. The chamber **528** is then purged again. The resulting SiN **420** is dense, has a low k-value of less than about 0.1, such as about 0.0, has atomic-scale thickness precession, and a low thermal budget.

(31) The carbon layer **418** is formed in a chemical vapor deposition (CVD) process, such as a PECVD process. FIG. 6 illustrates a graph **600** showing the k-value of the carbon layer **418** versus deposition temperature (C) when forming the carbon layer **418**, according to one embodiment. As shown in the graph **600**, when the deposition temperature is greater than about 275° C., a k-value of about 0.5 or greater is achieved. Thus, by adjusting the deposition conditions when forming the carbon layer **418** and/or doping the carbon layer **418** with a metal, the optical properties of the carbon layer **418** can be tuned to increase optical energy absorption and boost the recording performance of the write head **300**.

(32) Therefore, utilizing a MOC comprising a bilayer of carbon having a high k-value and SiN having a low k-value and a HOC comprising SiN having a low k-value within a magnetic recording device results in the HOC being transparent and the MOC being heat absorbing and eliminates negative impacts from the smear. Furthermore, the smear formed from the MOC and HOC during operation is transparent. The transparent HOC and the absorbing MOC increases the absorption in the media and reduces the laser power in the magnetic recording head, which reduces the temperature difference between the head and media surfaces and improves the reliability of the NFT.

(33) In one embodiment, a magnetic recording drive comprises a write head, the write head comprising a head overcoat disposed on a media facing surface (MFS), the head overcoat comprising SiN, and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a first layer of SiN disposed over a second layer of C.

(34) The head overcoat has an extinction coefficients (k) value of about 0.0. The media overcoat has a k-value of about 0.5 or greater. The head overcoat is transparent, and wherein the media overcoat is heat absorbent. The head overcoat has an extinction coefficient (k) value of less than or equal to about 0.1. The head overcoat is formed by atomic layer deposition (ALD).

(35) In another embodiment, a magnetic recording drive comprises a write head, the write head comprising: a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS), and a head overcoat disposed on the MFS, the head overcoat comprising SiN, and a head overcoat

disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having an extinction coefficients (k) value of about 0.0, and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a bilayer of SiN and C, with the C layer having a k-value of 0.5 or greater.

(36) The head overcoat is formed by atomic layer deposition (ALD). The SiN layer of the media overcoat is deposited using ALD, and wherein the C layer of the media overcoat is deposited using chemical vapor deposition. The SiN layer of the media overcoat is disposed over the C layer of the media overcoat. The head overcoat has an extinction coefficient (k) value of less than or equal to about 0.1. The head overcoat is transparent. The media overcoat is light absorbing.

(37) In yet another embodiment, a magnetic recording drive comprises a write head, the write head comprising: a main pole, a waveguide disposed adjacent to the main pole, a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS), and a transparent head overcoat disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having an extinction coefficients (k) value of less than about 0.1, and a media disposed adjacent to the MFS of the write head, the media comprising an absorbent media overcoat comprising a first layer of C and a second layer SiN, the first layer of C having a k-value of 0.5 or greater.

(38) The second layer of SiN is disposed on the first layer of C. The head overcoat and the second layer of SiN of the media overcoat are deposited by atomic layer deposition (ALD), and wherein the first layer of C of the media overcoat is deposited using chemical vapor deposition. The head overcoat has an extinction coefficients (k) value of about 0.0. The head overcoat is transparent, and wherein the media overcoat is heat absorbing.

(39) While the foregoing is directed to embodiments of the present disclosure, other and further embodiments of the disclosure may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow.

Claims

1. A magnetic recording drive, comprising: a write head, the write head comprising a head overcoat disposed on a media facing surface (MFS), the head overcoat comprising SiN; and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a first layer of SiN disposed over a second layer of C, wherein the media overcoat has an extinction coefficient (k) value of about 0.5 or greater.
2. The magnetic recording drive of claim 1, wherein the head overcoat has k-value of about 0.0.
3. The magnetic recording drive of claim 1, wherein the head overcoat is transparent.
4. The magnetic recording drive of claim 1, wherein the media overcoat is heat absorbent.
5. A magnetic recording drive, comprising: a write head, the write head comprising a head overcoat disposed on a media facing surface (MFS), the head overcoat comprising SiN; and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a first layer of SiN disposed over a second layer of C, wherein the head overcoat has an extinction coefficient (k) value of less than or equal to about 0.1.
6. The magnetic recording drive of claim 1, wherein the head overcoat is formed by atomic layer deposition (ALD).
7. A magnetic recording drive, comprising: a write head, the write head comprising: a main pole; a waveguide disposed adjacent to the main pole; a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS); and a head overcoat disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having an extinction coefficient (k) value of about 0.0; and a media disposed adjacent to the MFS of the write head, the media comprising a media overcoat comprising a bilayer of SiN and C, with the C layer having a k-value of 0.5 or greater.

8. The magnetic recording drive of claim 7, wherein the head overcoat is formed by atomic layer deposition (ALD).
 9. The magnetic recording drive of claim 7, wherein the SiN layer of the media overcoat is deposited using ALD, and wherein the C layer of the media overcoat is deposited using chemical vapor deposition.
 10. The magnetic recording drive of claim 7, wherein the SiN layer of the media overcoat is disposed over the C layer of the media overcoat.
 11. The magnetic recording drive of claim 7, further wherein the head overcoat has an extinction coefficient (k) value of less than or equal to about 0.1.
 12. The magnetic recording drive of claim 7, wherein the head overcoat is transparent.
 13. The magnetic recording drive of claim 7, wherein the media overcoat is heat absorbing.
 14. A magnetic recording drive, comprising: a write head, the write head comprising: a main pole; a waveguide disposed adjacent to the main pole; a near field transducer (NFT) coupled between the main pole and the waveguide at a media facing surface (MFS); and a transparent head overcoat disposed on the MFS adjacent to the NFT, the head overcoat comprising SiN and having an extinction coefficient (k) value of less than about 0.1; and a media disposed adjacent to the MFS of the write head, the media comprising a heat absorbent media overcoat comprising a first layer of C and a second layer SiN, the first layer of C having a k-value of 0.5 or greater.
 15. The magnetic recording drive of claim 14, wherein the head overcoat has an extinction coefficient (k) value of about 0.0.
 16. The magnetic recording drive of claim 14, wherein the second layer of SiN is disposed on the first layer of C.
 17. The magnetic recording drive of claim 14, wherein the head overcoat and the second layer of SiN of the media overcoat are deposited by atomic layer deposition (ALD).
 18. The magnetic recording drive of claim 14, wherein the first layer of C of the media overcoat is deposited using chemical vapor deposition.
 19. The magnetic recording drive of claim 14, wherein the head overcoat is transparent, and wherein the media overcoat is heat absorbing.
-