



US 20250279243A1

(19) **United States**

(12) **Patent Application Publication**
ITAMOCHI

(10) **Pub. No.: US 2025/0279243 A1**

(43) **Pub. Date: Sep. 4, 2025**

(54) **MULTILAYER CERAMIC ELECTRONIC COMPONENT**

(71) Applicant: **Murata Manufacturing Co., Ltd.**,
Nagaokakyo-shi (JP)

(72) Inventor: **Takeshi ITAMOCHI**, Nagaokakyo-shi
(JP)

(21) Appl. No.: **19/018,926**

(22) Filed: **Jan. 13, 2025**

(30) **Foreign Application Priority Data**

Mar. 4, 2024 (JP) 2024-032040

Publication Classification


(51) **Int. Cl.**
H01G 4/30 (2006.01)
H01G 2/06 (2006.01)
H01G 4/008 (2006.01)


H01G 4/012 (2006.01)
H01G 4/12 (2006.01)
H01G 4/232 (2006.01)

(52) **U.S. Cl.**
CPC **H01G 4/30** (2013.01); **H01G 2/065**
(2013.01); **H01G 4/008** (2013.01); **H01G**
4/012 (2013.01); **H01G 4/1227** (2013.01);
H01G 4/2325 (2013.01)

(57) **ABSTRACT**

A multilayer ceramic electronic component includes a multilayer body and a pair of external electrodes at both end portions of the multilayer body. The external electrodes include a main surface-side external electrode. The main surface-side external electrode includes a main surface-side base electrode layer, a main surface-side conductive resin layer above the main surface-side base electrode layer, and a main surface-side plated layer above the main surface-side conductive resin layer. The main surface-side conductive resin layer includes a conductive resin layer recess recessed towards a side of the multilayer body at a boundary interface with the main surface-side plated layer, in a cross-sectional view along the lamination direction and the length direction.





2
G
L





FIG. 3




4
FIG

FIG. 5A




FIG. 5B




FIG .6A




FIG .6B




FIG .6C




FIG. 7A




FIG. 7B





FIG .7C



MULTILAYER CERAMIC ELECTRONIC COMPONENT

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application is based on and claims the benefit of priority from Japanese Patent Application No. 2024-032040, filed on 4 Mar. 2024, the content of which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0002] The present invention relates to multilayer ceramic electronic components.

2. Description of the Related Art

[0003] Conventionally, multilayer ceramic capacitors as a multilayer ceramic electronic component are known. In recent years, multilayer ceramic capacitors have been required to endure harsh environments, such as those involving thermal expansion-induced flexure stress. A technique using a thermosetting conductive resin paste for the external electrodes of the multilayer ceramic capacitors is known to address this requirement. Japanese Unexamined Patent Application Publication No. H11-162771 exemplifies this type of technology. Japanese Unexamined Patent Application Publication No. H11-162771 discloses a multilayer ceramic capacitor including external electrodes with a layered structure, in which an electrode layer applied with a conductive paste by dipping and firing, a conductive epoxy-based thermosetting resin layer, a nickel plated layer, and a tin-based layer are sequentially stacked.

[0004] According to the multilayer ceramic capacitor of Japanese Unexamined Patent Application Publication No. H11-162771, the resin layer is sacrificially destructed and deformed to relieve the stress, thus allowing for reducing or preventing the occurrence of cracks in the multilayer body. However, in recent years, since durability in even more severe environments is required, the stress relief effect is less likely to function properly, potentially leading to cracks in the multilayer body.

SUMMARY OF THE INVENTION

[0005] Example embodiments of the present invention provide multilayer ceramic electronic components each able to reduce or prevent an occurrence of cracks in a multilayer body.

[0006] A multilayer ceramic capacitor according to an example embodiment of the present invention includes a multilayer body that includes a plurality of ceramic layers and a plurality of inner conductive layers stacked alternately in a height direction, a first main surface and a second main surface on opposite sides in the height direction, a first end surface and a second end surface on opposite sides in a length direction orthogonal or substantially orthogonal to the height direction, a first lateral surface and a second lateral surface on opposite sides in a width direction orthogonal or substantially orthogonal to both the height direction and the length direction, and a pair of external electrodes spaced apart from each other at both end portions of the multilayer body in the length direction. The inner conductive layers include a first inner conductive layer extending to the first

end surface and a second inner conductive layer extending to the second end surface. The external electrodes include a main surface-side external electrode on at least one of the first main surface or the second main surface. The main surface-side external electrode includes a main surface-side base electrode layer, a main surface-side conductive resin layer above the main surface-side base electrode layer, and a main surface-side plated layer above the main surface-side conductive resin layer. The main surface-side conductive resin layer includes a conductive resin layer recess recessed toward a side of the multilayer body at a boundary interface with the main surface-side plated layer, in a cross-sectional view along the height direction and the length direction.

[0007] Example embodiments of the present invention provide multilayer ceramic electronic components each able to reduce or prevent an occurrence of cracks in the multilayer body.

[0008] The above and other elements, features, steps, characteristics and advantages of the present invention will become more apparent from the following detailed description of the example embodiments with reference to the attached drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] FIG. 1 is a perspective view of a multilayer ceramic capacitor according to an example embodiment of the present invention.

[0010] FIG. 2 is a cross-sectional view taken along the line II-II of FIG. 1.

[0011] FIG. 3 is a cross-sectional view taken along the line III-III of FIG. 2.

[0012] FIG. 4 is a cross-sectional view taken along the line IV-IV of FIG. 2.

[0013] FIG. 5A is an enlarged view of the portion indicated by V in FIG. 2, illustrating a cross section of the first main surface-side external electrode.

[0014] FIG. 5B is an enlarged view of the portion indicated by V in FIG. 2, illustrating a cross section of the first main surface-side external electrode.

[0015] FIG. 6A is a diagram illustrating a method of manufacturing a multilayer ceramic capacitor according to an example embodiment of the present invention, illustrating a first step of forming an external electrode on a multilayer body.

[0016] FIG. 6B is a diagram illustrating a method of manufacturing a multilayer ceramic capacitor according to an example embodiment of the present invention, illustrating a second step of forming an external electrode on the multilayer body.

[0017] FIG. 6C is a diagram illustrating a method of manufacturing a multilayer ceramic capacitor according to an example embodiment of the present invention, illustrating a third step of forming an external electrode on the multilayer body.

[0018] FIG. 7A is a diagram illustrating a two-portion-structured multilayer ceramic capacitor.

[0019] FIG. 7B is a diagram illustrating a three-portion-structured multilayer ceramic capacitor.

[0020] FIG. 7C is a diagram illustrating a four-portion-structured multilayer ceramic capacitor.

DETAILED DESCRIPTION OF THE EXAMPLE EMBODIMENTS

[0021] Example embodiments of the present invention will be described in detail below with reference to the drawings.

[0022] Hereinafter, a multilayer ceramic capacitor 1 as a multilayer ceramic electronic component according to an example embodiment will be described with reference to FIGS. 1 to 4. FIG. 1 is a perspective view of the multilayer ceramic capacitor 1 according to the example embodiment. FIG. 2 is a cross-sectional view taken along the line II-II of the multilayer ceramic capacitor 1 in FIG. 1. FIG. 3 is a cross-sectional view taken along the line III-III of the multilayer ceramic capacitor 1 in FIG. 2. FIG. 4 is a cross-sectional view taken along the line IV-IV of the multilayer ceramic capacitor 1 in FIG. 2.

[0023] The multilayer ceramic capacitor 1 includes a multilayer body 10 and external electrodes 40.

[0024] FIGS. 1 to 4 illustrate an XYZ orthogonal coordinate system. The length direction L of the multilayer ceramic capacitor 1 and the multilayer body 10 corresponds to the X direction. The width direction W of the multilayer ceramic capacitor 1 and the multilayer body 10 corresponds to the Y direction. The lamination direction T as a height direction of the multilayer ceramic capacitor 1 and the multilayer body 10 corresponds to the Z direction. The cross section illustrated in FIG. 2 is also referred to as an LT cross section. The cross section illustrated in FIG. 3 is also referred to as a WT cross section. The cross section illustrated in FIG. 4 is also referred to as an LW cross section.

[0025] As illustrated in FIGS. 1 to 4, the multilayer body 10 includes a first main surface TS1 and a second main surface TS2 on opposite sides in the lamination direction T, a first lateral surface WS1 and a second lateral surface WS2 on opposite sides in the width direction W orthogonal or substantially orthogonal to the lamination direction T, and a first end surface LS1 and a second end surface LS2 on opposite sides in the length direction L orthogonal or substantially orthogonal to both the lamination direction T and the width direction W.

[0026] As illustrated in FIG. 1, the multilayer body 10 has a rectangular or substantially rectangular parallelepiped shape. The dimension in the length direction L of the multilayer body 10 is not necessarily longer than the dimension in the width direction W. The corners and edges of the multilayer body 10 are preferably rounded. The corners are where three faces of the multilayer body intersect, and the edges are where two faces of the multilayer body intersect. The surfaces of the multilayer body 10 may include irregularities in whole or in a portion thereof.

[0027] The dimensions of the multilayer body 10 are not particularly limited. However, the dimension of the multilayer body 10 in the length direction L, denoted as the L dimension, is, for example, preferably between about 0.2 mm and about 10 mm inclusive. The dimension of the multilayer body 10 in the lamination direction T, denoted as the T dimension, is, for example, preferably between about 0.1 mm and about 10 mm inclusive. The dimension of the multilayer body 10 in the width direction W, denoted as the W dimension, is, for example, preferably between about 0.1 mm and about 10 mm inclusive.

[0028] As illustrated in FIGS. 2 and 3, the multilayer body 10 includes an inner layer portion 11, and a first main surface-side outer layer portion 12A and a second main

surface-side outer layer portion 12B, with the inner layer portion 11 being interposed between the first main surface-side outer layer portion 12A and the second main surface-side outer layer portion 12B in the lamination direction T.

[0029] The inner layer portion 11 includes a plurality of dielectric layers 20 as a plurality of ceramic layers, and a plurality of internal electrode layers 30 as a plurality of inner conductive layers. The internal electrode layers 30 included in the inner layer portion 11 range from an internal electrode layer 30 closest to the first main surface TS1 to another internal electrode layer 30 closest to the second main surface TS2, in the lamination direction T. In the inner layer portion 11, the plurality of internal electrode layers 30 face each other via the dielectric layers 20. The inner layer portion 11 defines and functions to generate capacitance, and operates as a capacitor.

[0030] The dielectric layers 20 are made of dielectric materials. The dielectric materials may be dielectric ceramics including, for example, components such as BaTiO₃, CaTiO₃, SrTiO₃, or CaZrO₃. In addition to these main components, the dielectric materials may include accessory components such as, for example, Mn compounds, Fe compounds, Cr compounds, Co compounds, or Ni compounds.

[0031] The thickness of the dielectric layers 20 is, for example, preferably between about 0.5 μm and about 30 μm inclusive. The number of dielectric layers 20 to be stacked (laminated) is, for example, preferably between 10 and 1500 inclusive. The number of dielectric layers 20 is the total of the number of dielectric layers in the inner layer portion 11, and the number of the dielectric layers in the first main surface-side outer layer portion 12A and the second main surface-side outer layer portion 12B.

[0032] The plurality of internal electrode layers 30 include first internal electrode layers 31 as a plurality of first inner conductive layers, and second internal electrode layers 32 as a plurality of second inner conductive layers. The plurality of first internal electrode layers 31 are provided on the plurality of dielectric layers 20. The plurality of second internal electrode layers 32 are provided on the plurality of dielectric layers 20. The plurality of first internal electrode layers 31 and the plurality of second internal electrode layers 32 are alternately provided in the lamination direction T of the multilayer body 10, with the dielectric layers 20 being interposed therebetween. Each of the first internal electrode layers 31 and each of the second internal electrode layers 32 are provided such that a dielectric layer 20 of the dielectric layers 20 is interposed therebetween. Hereinafter, unless necessary to distinguish, the first internal electrode layers 31 and the second internal electrode layers 32 may collectively be referred to as the internal electrode layers 30.

[0033] The first internal electrode layer 31 includes a first counter portion 31A facing the second internal electrode layer 32, and a first extension portion 31B extending from the first counter portion 31A to the first end surface LS1. The first extension portion 31B is exposed at the first end surface LS1.

[0034] The second internal electrode layer 32 includes a second counter portion 32A facing the first internal electrode layer 31, and a second extension portion 32B extending from the second counter portion 32A to the second end surface LS2. The second extension portion 32B is exposed at the second end surface LS2.

[0035] In the present example embodiment, the first counter portion 31A and the second counter portion 32A face

each other, with the dielectric layer **20** being interposed therebetween, thus generating capacitance and providing the characteristics of the capacitor.

[0036] The shapes of the first counter portion **31A** and the second counter portion **32A** are not particularly limited, but are preferably rectangular or substantially rectangular. However, the corners of the rectangular-shaped portions may be rounded or formed diagonally. The shapes of the first extension portion **31B** and the second extension portion **32B** are not particularly limited, but are preferably rectangular or substantially rectangular. However, the corners of the rectangular-shaped portions may be rounded or formed diagonally.

[0037] Both of the dimensions of the first counter portion **31A** and the first extension portion **31B** in the width direction **W** may be the same or substantially the same, or one of the dimensions may be smaller. Both of the dimensions of the second counter portion **32A** and the second extension portion **32B** in the width direction **W** may be the same or substantially the same, or one of the dimensions may be smaller.

[0038] The first internal electrode layers **31** and the second internal electrode layers **32** are made of appropriate conductive materials such as, for example, metals like Ni, Cu, Ag, Pd, Au, or alloys including at least one of these metals. When using an alloy, for example, the first internal electrode layers **31** and the second internal electrode layers **32** may be made of Ag—Pd alloy.

[0039] The thickness of the first internal electrode layers **31** and the second internal electrode layers **32** is, for example, preferably approximately between about 0.2 μm and about 2.0 μm inclusive. The total number of the first internal electrode layers **31** and the second internal electrode layers **32** is, for example, preferably between 10 and 1500 inclusive.

[0040] The first main surface-side outer layer portion **12A** is provided on the first main surface **TS1** side of the multilayer body **10**. The first main surface-side outer layer portion **12A** is a collective portion including the plurality of dielectric layers **20** between the first main surface **TS1** and the internal electrode layer **30** closest to the first main surface **TS1**. The dielectric layers **20** used in the first main surface-side outer layer portion **12A** may be the same as the dielectric layers **20** used in the inner layer portion **11**, or may be dielectric layers made of different materials.

[0041] The second main surface-side outer layer portion **12B** is provided on the second main surface **TS2** side of the multilayer body **10**. The second main surface-side outer layer portion **12B** is a collective portion including the plurality of dielectric layers **20** between the second main surface **TS2** and the internal electrode layer **30** closest to the second main surface **TS2**. The dielectric layers **20** used in the second main surface-side outer layer portion **12B** may be the same as the dielectric layers **20** used in the inner layer portion **11**, or may be dielectric layers made of different materials.

[0042] The multilayer body **10** includes a counter electrode portion **11E**. The counter electrode portion **11E** is a portion where the first counter portion **31A** of the first internal electrode layer **31** faces the second counter portion **32A** of the second internal electrode layer **32**. The counter electrode portion **11E** is a portion of the inner layer portion **11**. FIG. 4 illustrates the range of the counter electrode

portion **11E** in the width direction **W** and the length direction **L**. The counter electrode portion **11E** is also referred to as the capacitor active portion.

[0043] The multilayer body **10** includes lateral surface-side outer layer portions **WG**. The lateral surface-side outer layer portions **WG** include a first lateral surface-side outer layer portion **WG1** and a second lateral surface-side outer layer portion **WG2**. The first lateral surface-side outer layer portion **WG1** is a portion including the dielectric layers **20** between the counter electrode portion **11E** and the first lateral surface **WS1**. The second lateral surface-side outer layer portion **WG2** is a portion including the dielectric layers **20** between the counter electrode portion **11E** and the second lateral surface **WS2**. FIGS. 3 and 4 illustrate the range of the first lateral surface-side outer layer portion **WG1** and the second lateral surface-side outer layer portion **WG2** in the width direction **W**. The lateral surface-side outer layer portions are also referred to as **W** gaps or side gaps.

[0044] The multilayer body **10** includes end surface-side outer layer portions **LG**. The end surface-side outer layer portions **LG** include a first end surface-side outer layer portion **LG1** and a second end surface-side outer layer portion **LG2**. The first end surface-side outer layer portion **LG1** is a portion including the dielectric layers **20** between the counter electrode portion **11E** and the first end surface **LS1**. The second end surface-side outer layer portion **LG2** is a portion including the dielectric layers **20** between the counter electrode portion **11E** and the second end surface **LS2**. FIGS. 2 and 4 illustrate the range of the first end surface-side outer layer portion **LG1** and the second end surface-side outer layer portion **LG2** in the length direction **L**. The end surface-side outer layer portions are also referred to as **L** gaps or end gaps.

[0045] The external electrodes **40** include a first external electrode **40A** on the first end surface **LS1** side, and a second external electrode **40B** on the second end surface **LS2** side.

[0046] The first external electrode **40A** is provided on the first end surface **LS1**. The first external electrode **40A** is connected to the first internal electrode layer **31**. The first external electrode **40A** is provided on a portion of the first main surface **TS1** and a portion of the second main surface **TS2**. In the example embodiment, the first external electrode **40A** extends from the first end surface **LS1** to a portion of the first main surface **TS1** and a portion of the second main surface **TS2**, a portion of the first lateral surface **WS1**, and a portion of the second lateral surface **WS2**.

[0047] The second external electrode **40B** is provided on the second end surface **LS2**. The second external electrode **40B** is connected to the second internal electrode layer **32**. The second external electrode **40B** is provided on a portion of the first main surface **TS1** and a portion of the second main surface **TS2**. In the example embodiment, the second external electrode **40B** extends from the second end surface **LS2** to a portion of the first main surface **TS1** and a portion of the second main surface **TS2**, a portion of the first lateral surface **WS1**, and a portion of the second lateral surface **WS2**.

[0048] As described above, within the multilayer body **10**, the first counter portion **31A** of the first internal electrode layer **31** faces the second counter portion **32A** of the second internal electrode layer **32**, with the dielectric layer **20** being interposed therebetween, thus generating the capacitance. Therefore, capacitor characteristics are provided between the first external electrode **40A** connected to the first internal

electrode layer 31, and the second external electrode 40B connected to the second internal electrode layer 32.

[0049] The first external electrode 40A includes a first base electrode layer 50A including metal components, a first conductive resin layer 60A on the first base electrode layer 50A, and a first plated layer 70A on the first conductive resin layer 60A. The first plated layer 70A includes, for example, a first Ni plated layer 71A as the lower plated layer and a first Sn plated layer 72A as the upper plated layer.

[0050] The second external electrode 40B includes a second base electrode layer 50B including metal components, a second conductive resin layer 60B on the second base electrode layer 50B, and a second plated layer 70B on the second conductive resin layer 60B. The second plated layer 70B includes, for example, a second Ni plated layer 71B as the lower plated layer and a second Sn plated layer 72B as the upper plated layer.

[0051] Here, the basic configuration of each layer of the first external electrode 40A and the second external electrode 40B is the same or substantially the same. The first external electrode 40A and the second external electrode 40B are substantially plane-symmetrical with respect to the LW cross section at the center of the multilayer ceramic capacitor 1 in the length direction L. Therefore, unless necessary to distinguish, the first external electrode 40A and the second external electrode 40B may be collectively referred to as the external electrodes 40. Similarly, unless necessary to distinguish, the first base electrode layer 50A and the second base electrode layer 50B may be collectively referred to as the base electrode layers 50. Unless necessary to distinguish, the first conductive resin layer 60A and the second conductive resin layer 60B may be collectively referred to as the conductive resin layers 60. Unless necessary to distinguish, the first plated layer 70A and the second plated layer 70B may be collectively referred to as the plated layers 70. Unless necessary to distinguish, the first Ni plated layer 71A and the second Ni plated layer 71B may be collectively referred to as the Ni plated layers 71. Unless necessary to distinguish, the first Sn plated layer 72A and the second Sn plated layer 72B may be collectively referred to as the Sn plated layers 72.

[0052] The base electrode layer 50 includes the first base electrode layer 50A and the second base electrode layer 50B.

[0053] The first base electrode layer 50A is provided on the first end surface LS1. The first base electrode layer 50A is connected to the first internal electrode layers 31. In the present example embodiment, the first base electrode layer 50A extends from the first end surface LS1 to a portion of the first main surface TS1, a portion of the second main surface TS2, a portion of the first lateral surface WS1, and a portion of the second lateral surface WS2.

[0054] The second base electrode layer 50B is provided on the second end surface LS2. The second base electrode layer 50B is in contact with the second internal electrode layers 32. In the present example embodiment, the second base electrode layer 50B extends from the second end surface LS2 to a portion of the first main surface TS1, a portion of the second main surface TS2, a portion of the first lateral surface WS1, and a portion of the second lateral surface WS2.

[0055] The first base electrode layer 50A and the second base electrode layer 50B of the present example embodiment are fired layers. The fired layer preferably includes, for example, a metal component and either a glass component

or a ceramic component, or both. This can improve the adhesion between the multilayer body 10 and the base electrode layers. The metal component may include, for example, at least one of Cu, Ni, Ag, Pd, Ag—Pd alloy, or Au. The glass component may include, for example, at least one of B, Si, Ba, Mg, Al, or Li. The glass component being present can aid and promote sintering of the metal components within the base electrode layer. The ceramic component may use the same ceramic material as the dielectric layer 20 or a different type of ceramic material. Examples of the ceramic component include at least one of BaTiO₃, CaTiO₃, (Ba, Ca)TiO₃, SrTiO₃, or CaZrO₃.

[0056] The fired layer, for example, is prepared by applying a conductive paste including glass and metal to the multilayer body, followed by firing. The fired layer may be prepared by simultaneously firing the multilayer chips including internal electrodes and dielectric layers, and the conductive paste applied to the multilayer chips, or may be prepared by obtaining the multilayer body by firing the multilayer chips including internal electrodes and dielectric layers, and then applying the conductive paste to the multilayer body, followed by firing. In the case of simultaneously firing the multilayer chip including internal electrodes and dielectric layers, and the conductive paste applied to the multilayer chip, the fired layer is, for example, preferably formed by firing a mixture including ceramic material instead of a glass component. In this case, as the ceramic material to be added, using a ceramic material the same as or similar to the dielectric layer 20 is preferable. The fired layer may include a plurality of layers.

[0057] The thickness of the first base electrode layer 50A on the first end surface LS1 in the length direction L is, for example, preferably between about 2 μm and about 220 μm inclusive at the center of the first base electrode layer 50A in the lamination direction T and the width direction W.

[0058] The thickness of the second base electrode layer 50B on the second end surface LS2 in the length direction L is, for example, preferably between about 2 μm and about 220 μm inclusive at the center of the second base electrode layer 50B in the lamination direction T and the width direction W.

[0059] In cases where the first base electrode layer 50A is also provided on a portion of at least one of the first main surface TS1 or the second main surface TS2, the thickness of the first base electrode layer 50A in this portion in the lamination direction T is, for example, preferably between about 3 μm and about 40 μm inclusive at the center of the first base electrode layer 50A in this portion in the length direction L and the width direction W.

[0060] In cases where the first base electrode layer 50A is also provided on a portion of at least one of the first lateral surface WS1 or the second lateral surface WS2, the thickness of the first base electrode layer 50A in this portion in the width direction W is, for example, preferably between about 3 μm and about 40 μm inclusive at the center of the first base electrode layer 50A in this portion in the length direction L and the lamination direction T.

[0061] In cases where the second base electrode layer 50B is also provided on a portion of at least one of the first main surface TS1 or the second main surface TS2, the thickness of the second base electrode layer 50B in this portion in the lamination direction T is, for example, preferably between about 3 μm and about 40 μm inclusive at the center of the

second base electrode layer **50B** in this portion in the length direction L and the width direction W.

[0062] In cases where the second base electrode layer **50B** is also provided on a portion of at least one of the first lateral surface **WS1** or the second lateral surface **WS2**, the thickness of the second base electrode layer **50B** in this portion in the width direction W is, for example, preferably between about 3 μm and about 40 μm inclusive at the center of the second base electrode layer **50B** in this portion in the length direction L and the lamination direction T.

[0063] The external electrode **40** includes the conductive resin layer **60**, which includes resin components and metal components, on the base electrode layer **50**.

[0064] The conductive resin layer **60** includes the first conductive resin layer **60A** and the second conductive resin layer **60B**.

[0065] The first conductive resin layer **60A** covers the first base electrode layer **50A**. In the present example embodiment, the first conductive resin layer **60A** extends from the first end surface **LS1** to a portion of the first main surface **TS1** and the second main surface **TS2**, and a portion of the first lateral surface **WS1** and the second lateral surface **WS2**. The second conductive resin layer **60B** covers the second base electrode layer **50B**. In the present example embodiment, the second conductive resin layer **60B** extends from the second end surface **LS2** to a portion of the first main surface **TS1** and the second main surface **TS2**, and a portion of the first lateral surface **WS1** and the second lateral surface **WS2**. The dimension of the first conductive resin layer **60A** on the first main surface **TS1** and the second main surface **TS2** in the length direction L is longer than the dimension of the first base electrode layer **50A** on the first main surface **TS1** and the second main surface **TS2** in the length direction L. The dimension of the second conductive resin layer **60B** on the first main surface **TS1** and the second main surface **TS2** in the length direction L is longer than the dimension of the second base electrode layer **50B** on the first main surface **TS1** and the second main surface **TS2** in the length direction L.

[0066] The thickness of the first conductive resin layer **60A** on the first end surface **LS1** side in the length direction L is, for example, preferably between about 5 μm and about 200 μm inclusive at the central portion of the first conductive resin layer **60A** in the lamination direction T and width direction W.

[0067] The thickness of the second conductive resin layer **60B** on the second end surface **LS2** side in the length direction L is, for example, preferably approximately between 5 μm and 200 μm inclusive at the central portion of the second conductive resin layer **60B** in the lamination direction T and width direction W.

[0068] In the case where the first conductive resin layer **60A** is also provided on a portion of the first main surface **TS1** side and a portion of the second main surface **TS2** side, the thickness of the first conductive resin layer **60A** in this portion in the lamination direction T is, for example, preferably approximately between 5 μm and 200 μm inclusive at the central portion of the first conductive resin layer **60A** in the length direction L and width direction W.

[0069] In the case where the first conductive resin layer **60A** is also provided on a portion of the first lateral surface **WS1** side and a portion of the second lateral surface **WS2** side, the thickness of the first conductive resin layer **60A** in this portion in the width direction is, for example, preferably

between about 5 μm and about 200 μm inclusive at the central portion of the first conductive resin layer **60A** in the length direction L and lamination direction T.

[0070] In the case where the second conductive resin layer **60B** is also provided on a portion of the first main surface **TS1** side and a portion of the second main surface **TS2** side, the thickness of the second conductive resin layer **60B** in this portion in the lamination direction T is, for example, preferably between about 5 μm and about 200 μm inclusive at the central portion of the second conductive resin layer **60B** in the length direction L and width direction W.

[0071] In the case where the second conductive resin layer **60B** is also provided on a portion of the first lateral surface **WS1** side and a portion of the second lateral surface **WS2** side, the thickness of the second conductive resin layer **60B** in this portion in the width direction is, for example, preferably between about 5 μm and about 200 μm inclusive, at the central portion of the second conductive resin layer **60B** in the length direction L and lamination direction T.

[0072] The conductive resin layer **60** is provided on the base electrode layer **50**. The plated layer **70** covers the conductive resin layer **60**. The plated layer **70** includes, for example, the Ni plated layer **71** and the Sn plated layer **72**.

[0073] The conductive resin layer **60** includes, for example, a resin portion as resin components, and conductive fillers as filler particles dispersed within the resin portion.

[0074] The resin portion of the conductive resin layer **60** may include, for example, at least one of various known thermosetting resins such as epoxy resin, phenoxym resin, phenol resin, urethane resin, silicone resin, polyimide resin, etc. Among these, epoxy resin, which has excellent heat resistance, moisture resistance, and adhesiveness, is one of the more preferable resins. The resin portion of the conductive resin layer **60** preferably includes a curing agent, along with the thermosetting resin. In the case of using epoxy resin as the base resin, the curing agent for the epoxy resin may be, for example, various known compounds such as phenolic, amine, anhydride, imidazole, active ester, and amide-imide compounds.

[0075] The conductive resin layer **60**, including such a resin portion, is more flexible than the base electrode layer **50** including a plating film or a fired material of metal components and glass components. Therefore, the conductive resin layer **60** defines and functions as a buffering layer even when the multilayer ceramic capacitor **1** is subjected to physical shock or thermal-cycling shock. Thus, the conductive resin layer **60** reduces or prevents the occurrence of cracks in the multilayer ceramic capacitor **1**.

[0076] The conductive fillers are dispersed substantially uniformly within the resin portion. The conductive fillers primarily ensure the conductivity of the conductive resin layer **60**. Specifically, contact between a plurality of conductive fillers provides conductive pathways within the conductive resin layer **60**, ensuring electrical conductivity between the base electrode layer **50** and the plated layer **70**.

[0077] The metal of the conductive filler may be, for example, pure Ag, an alloy including Ag, or metal powders coated with Ag on their surface. Ag, the resistivity of which is the lowest among metals, is suitable as an electrode material. Being a noble metal, Ag is less prone to oxidation and has high weather resistance. Therefore, Ag metal powders are suitable as conductive fillers. When using metal

powders coated with Ag on their surface, it is preferable to use, for example, Cu, Ni, Sn, Bi, or their alloy powders.

[0078] The conductive fillers may be, for example, Cu or Ni subjected to an antioxidation treatment. The conductive fillers may also be, for example, metal powders coated with Sn, Ni, Cu on their surface. When using metal powders coated with Sn, Ni, Cu on their surface, the metal powders are, for example, preferably Ag, Cu, Ni, Sn, Bi, or their alloys. The conductive fillers preferably include, for example, a core of Cu particles. At least a portion of the surface of the Cu particles is, for example, preferably coated with a Cu-Ag alloy of Cu and Ag. At least a portion of the surface of the Cu particles may be coated with Ag, for example. This improves the affinity with Ni plating and improves electrical properties.

[0079] The shape of the conductive fillers is not particularly limited. The shape of the conductive fillers can be spherical, flat, etc. It is preferable to use a mixture of spherical and flat metal powders. In other words, the conductive fillers as filler powders include flat powders or spherical powders.

[0080] The average particle size of the conductive fillers may be, for example, between about 0.3 μm and about 10 μm inclusive.

[0081] An example of a method of measuring the average particle size of the conductive fillers included in the conductive resin layer 60 is calculated using a laser diffraction particle size measurement method, based on ISO 13320, instead of the shape of the conductive fillers.

[0082] The plated layer 70 includes the first plated layer 70A and the second plated layer 70B.

[0083] The first plated layer 70A covers the first conductive resin layer 60A. In the present example embodiment, the first plated layer 70A extends from the first end surface LS1 to a portion of the first main surface TS1 and the second main surface TS2, and a portion of the first lateral surface WS1 and the second lateral surface WS2.

[0084] The second plated layer 70B covers the second conductive resin layer 60B. In the present example embodiment, the second plated layer 70B extends from the first end surface LS1 to a portion of the first main surface TS1 and the second main surface TS2, and a portion of the first lateral surface WS1 and the second lateral surface WS2.

[0085] The plated layer 70 preferably includes a two-layer structure including the Ni plated layer 71 and the Sn plated layer 72, for example. The first Sn plated layer 72A is preferably provided on the first Ni plated layer 71A, and the second Sn plated layer 72B is preferably provided on the second Ni plated layer 71B. The Ni plated layer 71 prevents the base electrode layer 50 and the conductive resin layer 60 from being eroded by solder when mounting the multilayer ceramic capacitor 1. The Sn plated layer 72 improves the solder wettability when mounting the multilayer ceramic capacitor 1. This facilitates the mounting process of the multilayer ceramic capacitor 1.

[0086] The thickness of the first Ni plated layer 71A and the first Sn plated layer 72A is, for example, preferably between about 1 μm and about 15 μm inclusive.

[0087] The thickness of the second Ni plated layer 71B and the second Sn plated layer 72B is, for example, preferably between about 1 μm and about 15 μm inclusive.

[0088] The basic configuration of the multilayer ceramic capacitor 1 according to the present example embodiment has been described above. The dimension of the multilayer

ceramic capacitor 1 including the multilayer body 10 and the external electrodes 40 in the length direction L, denoted as the L dimension, is, for example, preferably between about 0.2 mm and about 10 mm inclusive. The dimension of the multilayer ceramic capacitor 1 in the lamination direction T, denoted as the T dimension, is, for example, preferably between about 0.05 mm and about 10 mm inclusive. The dimension of the multilayer ceramic capacitor 1 in the width direction W, denoted as the W dimension, is, for example, preferably between about 0.1 mm and about 10 mm inclusive.

[0089] The multilayer ceramic capacitor 1 of the present example embodiment including the basic configuration has the following configurations in the external electrodes 40, which include the first external electrode 40A and the second external electrode 40B.

[0090] The external electrodes 40 of the present example embodiment include the main surface-side external electrodes on at least one of the first main surface TS1 or the second main surface TS2. Specifically, as described above, the first external electrode 40A of the present example embodiment is provided on the first end surface LS1 and extends from the first end surface LS1 to a portion of the first main surface TS1, a portion of the second main surface TS2, a portion of the first lateral surface WS1, and a portion of the second lateral surface WS2. The first external electrode 40A of the present example embodiment includes a first end surface-side external electrode 400A as an end surface-side external electrode on the first end surface LS1, a first main surface-side external electrode 411A as a main surface-side external electrode on the first main surface TS1, a second main surface-side external electrode 412A as a main surface-side external electrode on the second main surface TS2, as illustrated in FIGS. 2 and 4, a first lateral surface-side external electrode 421A on the first lateral surface WS1, and a second lateral surface-side external electrode 422A on the second lateral surface WS2, as illustrated in FIG. 4.

[0091] As described earlier, the first external electrode 40A includes the first base electrode layer 50A, the first conductive resin layer 60A on the first base electrode layer 50A, and the first plated layer 70A on the first conductive resin layer 60A. In the present example embodiment, the first base electrode layer 50A extends from the first end surface LS1 to a portion of the first main surface TS1 and the second main surface TS2, and a portion of the first lateral surface WS1 and the second lateral surface WS2. The first conductive resin layer 60A covers the first base electrode layer 50A, and the first plated layer 70A covers the first conductive resin layer 60A.

[0092] In other words, as illustrated in FIGS. 2 and 4, the first end surface-side external electrode 400A of the present example embodiment includes the first end surface-side base electrode layer 500A on the first end surface LS1, the first end surface-side conductive resin layer 600A above the first end surface-side base electrode layer 500A, and the first end surface-side plated layer 700A above the first end surface-side conductive resin layer 600A. The first end surface-side base electrode layer 500A is a portion of the first base electrode layer 50A. The first end surface-side conductive resin layer 600A is a portion of the first conductive resin layer 60A. The first end surface-side plated layer 700A is a portion of the first plated layer 70A, and includes the first Ni plated layer 71A and the first Sn plated layer 72A on the first Ni plated layer 71A.

[0093] As illustrated in FIG. 2, the first main surface-side external electrode 411A of the present example embodiment includes the first main surface-side base electrode layer 511A as the main surface-side base electrode layer on the first main surface TS1, the first main surface-side conductive resin layer 611A as the main surface-side conductive resin layer above the first main surface-side base electrode layer 511A, and the first main surface-side plated layer 711A as the main surface-side plated layer above the first main surface-side conductive resin layer 611A. The first main surface-side base electrode layer 511A is a portion of the first base electrode layer 50A. The first main surface-side conductive resin layer 611A is a portion of the first conductive resin layer 60A. The first main surface-side plated layer 711A is a portion of the first plated layer 70A, and includes the first Ni plated layer 71A and the first Sn plated layer 72A on the first Ni plated layer 71A.

[0094] As illustrated in FIG. 2, the second main surface-side external electrode 412A of the present example embodiment includes the second main surface-side base electrode layer 512A as the main surface-side base electrode layer on the second main surface TS2, the second main surface-side conductive resin layer 612A as the main surface-side conductive resin layer above the second main surface-side base electrode layer 512A, and the second main surface-side plated layer 712A as the main surface-side plated layer above the second main surface-side conductive resin layer 612A. The second main surface-side base electrode layer 512A is a portion of the first base electrode layer 50A. The second main surface-side conductive resin layer 612A is a portion of the first conductive resin layer 60A. The second main surface-side plated layer 712A is a portion of the first plated layer 70A, and includes the first Ni plated layer 71A and the first Sn plated layer 72A on the first Ni plated layer 71A.

[0095] As illustrated in FIG. 4, the first lateral surface-side external electrode 421A of the present example embodiment includes the first lateral surface-side base electrode layer 521A on the first lateral surface WS1, the first lateral surface-side conductive resin layer 621A above the first lateral surface-side base electrode layer 521A, and the first lateral surface-side plated layer 721A above the first lateral surface-side conductive resin layer 621A. The first lateral surface-side base electrode layer 521A is a portion of the first base electrode layer 50A. The first lateral surface-side conductive resin layer 621A is a portion of the first conductive resin layer 60A. The first lateral surface-side plated layer 721A is a portion of the first plated layer 70A, and includes the first Ni plated layer 71A and the first Sn plated layer 72A on the first Ni plated layer 71A.

[0096] As illustrated in FIG. 4, the second lateral surface-side external electrode 422A of the present example embodiment includes the second lateral surface-side base electrode layer 522A on the second lateral surface WS2, the second lateral surface-side conductive resin layer 622A above the second lateral surface-side base electrode layer 522A, and the second lateral surface-side plated layer 722A above the second lateral surface-side conductive resin layer 622A. The second lateral surface-side base electrode layer 522A is a portion of the first base electrode layer 50A. The second lateral surface-side conductive resin layer 622A is a portion of the first conductive resin layer 60A. The second lateral surface-side plated layer 722A is a portion of the first plated

layer 70A, and includes the first Ni plated layer 71A and the first Sn plated layer 72A on the first Ni plated layer 71A.

[0097] The thickness of the first main surface-side base electrode layer 511A, the second main surface-side base electrode layer 512A, the first lateral surface-side base electrode layer 521A, and the second lateral surface-side base electrode layer 522A is, for example, preferably between about 5 μm and about 10 μm inclusive.

[0098] The thickness of the first Ni plated layer 71A and the first Sn plated layer 72A, in the first main surface-side plated layer 711A, the second main surface-side plated layer 712A, the first lateral surface-side plated layer 721A, and the second lateral surface-side plated layer 722A, is, for example, preferably between about 1 μm and about 4 μm inclusive.

[0099] As described above, the second external electrode 40B of the example embodiment is provided on the second end surface LS2 and extends from the second end surface LS2 to a portion of the first main surface TS1, a portion of the second main surface TS2, a portion of the first lateral surface WS1, and a portion of the second lateral surface WS2. Specifically, the second external electrode 40B of the present example embodiment includes a second end surface-side external electrode 400B as an end surface-side external electrode on the second end surface LS1, a first main surface-side external electrode 411B as a main surface-side external electrode on the first main surface TS1, a second main surface-side external electrode 412B as a main surface-side external electrode on the second main surface TS2, as illustrated in FIG. 2, a first lateral surface-side external electrode 421B on the first lateral surface WS1, and a second lateral surface-side external electrode 422B on the second lateral surface WS2, as illustrated in FIG. 4.

[0100] As described earlier, the second external electrode 40B includes the second base electrode layer 50B, the second conductive resin layer 60B on the second base electrode layer 50B, and the second plated layer 70B on the second conductive resin layer 60B. In the present example embodiment, the second base electrode layer 50B extends from the second end surface LS2 to a portion of the first main surface TS1 and the second main surface TS2, and a portion of the first lateral surface WS1 and the second lateral surface WS2. The second conductive resin layer 60B covers the second base electrode layer 50B, and the second plated layer 70B covers the second conductive resin layer 60B.

[0101] In other words, as illustrated in FIGS. 2 and 4, the second end surface-side external electrode 400B of the present example embodiment includes the second end surface-side base electrode layer 500B on the second end surface LS2, the second end surface-side conductive resin layer 600B above the second end surface-side base electrode layer 500B, and the second end surface-side plated layer 700B above the second end surface-side conductive resin layer 600B. The second end surface-side base electrode layer 500B is a portion of the second base electrode layer 50B. The second end surface-side conductive resin layer 600B is a portion of the second conductive resin layer 60B. The second end surface-side plated layer 700B is a portion of the second plated layer 70B, and includes the second Ni plated layer 71B and the second Sn plated layer 72B on the second Ni plated layer 71B.

[0102] As illustrated in FIG. 2, the first main surface-side external electrode 411B of the present example embodiment includes the first main surface-side base electrode layer

511B as the main surface-side base electrode layer on the first main surface **TS1**, the first main surface-side conductive resin layer **611B** as the main surface-side conductive resin layer above the first main surface-side base electrode layer **511B**, and the first main surface-side plated layer **711B** as the main surface-side plated layer above the first main surface-side conductive resin layer **611B**. The first main surface-side base electrode layer **511B** is a portion of the second base electrode layer **50B**. The first main surface-side conductive resin layer **611B** is a portion of the second conductive resin layer **60B**. The first main surface-side plated layer **711B** is a portion of the second plated layer **70B**, and includes the second Ni plated layer **71B** and the second Sn plated layer **72B** on the second Ni plated layer **71B**.

[0103] As illustrated in FIG. 2, the second main surface-side external electrode **412B** of the present example embodiment includes the second main surface-side base electrode layer **512B** as the main surface-side base electrode layer on the second main surface **TS2**, the second main surface-side conductive resin layer **612B** as the main surface-side conductive resin layer above the second main surface-side base electrode layer **512B**, and the second main surface-side plated layer **712B** as the main surface-side plated layer above the second main surface-side conductive resin layer **612B**. The second main surface-side base electrode layer **512B** is a portion of the second base electrode layer **50B**. The second main surface-side conductive resin layer **612B** is a portion of the second conductive resin layer **60B**. The second main surface-side plated layer **712B** is a portion of the second plated layer **70B**, and includes the second Ni plated layer **71B** and the second Sn plated layer **72B** on the second Ni plated layer **71B**.

[0104] As illustrated in FIG. 4, the first lateral surface-side external electrode **421B** of the present example embodiment includes the first lateral surface-side base electrode layer **521B** on the first lateral surface **WS1**, the first lateral surface-side conductive resin layer **621B** above the first lateral surface-side base electrode layer **521B**, and the first lateral surface-side plated layer **721B** above the first lateral surface-side conductive resin layer **621B**. The first lateral surface-side base electrode layer **521B** is a portion of the second base electrode layer **50B**. The first lateral surface-side conductive resin layer **621B** is a portion of the second conductive resin layer **60B**. The first lateral surface-side plated layer **721B** is a portion of the second plated layer **70B**, and includes the second Ni plated layer **71B** and the second Sn plated layer **72B** on the second Ni plated layer **71B**.

[0105] As illustrated in FIG. 4, the second lateral surface-side external electrode **422B** of the present example embodiment includes the second lateral surface-side base electrode layer **522B** on the second lateral surface **WS2**, the second lateral surface-side conductive resin layer **622B** above the second lateral surface-side base electrode layer **522B**, and the second lateral surface-side plated layer **722B** above the second lateral surface-side conductive resin layer **622B**. The second lateral surface-side base electrode layer **522B** is a portion of the second base electrode layer **50B**. The second lateral surface-side conductive resin layer **622B** is a portion of the second conductive resin layer **60B**. The second lateral surface-side plated layer **722B** is a portion of the second plated layer **70B**, and includes the second Ni plated layer **71B** and the second Sn plated layer **72B** on the second Ni plated layer **71B**.

[0106] The thickness of the first main surface-side base electrode layer **511B**, the second main surface-side base electrode layer **512B**, the first lateral surface-side base electrode layer **521B**, and the second lateral surface-side base electrode layer **522B** is, for example, preferably between about 5 μm and about 10 μm inclusive.

[0107] The thickness of the second Ni plated layer **71B** and the second Sn plated layer **72B** of the first main surface-side plated layer **711B**, the second main surface-side plated layer **712B**, the first lateral surface-side plated layer **721B**, and the second lateral surface-side plated layer **722B** is preferably, for example, between about 1 μm and about 4 μm inclusive.

[0108] FIG. 2 illustrates the LT cross section of the multilayer ceramic capacitor **1** and the multilayer body **10** along the lamination direction **T** and the length direction **L**. In the LT cross-sectional view, the first main surface-side external electrode **411A** of the first external electrode **40A** includes a first main surface-side recess **510A** recessed towards the multilayer body **10** side. The first main surface-side recess **510A** is provided on the surface of the first main surface-side external electrode **411A**. The shape of the first main surface-side recess **510A** is a groove extending in the width direction **W** orthogonal or substantially orthogonal to the LT cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 2. The first main surface-side recess **510A** may be provided over the entire or substantially the entire length of the first main surface-side external electrode **411A** along the width direction **W**. The first main surface-side recess **510A** is provided near the approximate center of the first main surface-side external electrode **411A** in the length direction **L**.

[0109] As illustrated in FIG. 2, the second main surface-side external electrode **412A** of the first external electrode **40A** includes a second main surface-side recess **520A** recessed towards the multilayer body **10** side in the LT cross-sectional view. The second main surface-side recess **520A** is provided on the surface of the second main surface-side external electrode **412A**. The shape of the second main surface-side recess **520A** is a groove extending in the width direction **W** orthogonal or substantially orthogonal to the LT cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 2. The second main surface-side recess **520A** may be provided over the entire or substantially the entire length of the second main surface-side external electrode **412A** along the width direction **W**.

[0110] The second main surface-side recess **520A** is provided near the approximate center of the second main surface-side external electrode **412A** in the length direction **L**.

[0111] As illustrated in FIG. 2, the first main surface-side external electrode **411B** of the second external electrode **40B** includes a first main surface-side recess **510B** recessed towards the multilayer body **10** side in the LT cross-sectional view. The first main surface-side recess **510B** is provided on the surface of the first main surface-side external electrode **411B**. The shape of the first main surface-side recess **510B** is a groove extending in the width direction **W** orthogonal or substantially orthogonal to the LT cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 2. The first main surface-side recess **510B** may be provided over the entire or substantially the entire length of the first main surface-side external electrode

411B along the width direction **W**. The first main surface-side recess **510B** is provided near the approximate center of the first main surface-side external electrode **411B** in the length direction **L**.

[0112] As illustrated in FIG. 2, the second main surface-side external electrode **412B** of the second external electrode **40B** includes a second main surface-side recess **520B** recessed towards the multilayer body **10** side in the LT cross-sectional view. The second main surface-side recess **520B** is provided on the surface of the second main surface-side external electrode **412B**. The shape of the second main surface-side recess **520B** is a groove extending in the width direction **W** orthogonal or substantially orthogonal to the LT cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 2. The second main surface-side recess **520B** may be provided over the entire or substantially the entire length of the second main surface-side external electrode **412B** along the width direction **W**. The second main surface-side recess **520B** is provided near the approximate center of the second main surface-side external electrode **412B** in the length direction **L**.

[0113] FIG. 4 illustrates an LW cross section of the multilayer ceramic capacitor **1** and the multilayer body **10** along the length direction **L** and the width direction **W**. In the LW cross-sectional views, the first lateral surface-side external electrode **421A** of the first external electrode **40A** includes a first lateral surface-side recess **530A** recessed towards the multilayer body **10** side. The first lateral surface-side recess **530A** is provided on the surface of the first lateral surface-side external electrode **421A**. The shape of the first lateral surface-side recess **530A** is a groove extending in the lamination direction **T** orthogonal or substantially orthogonal to the LW cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 4. The first lateral surface-side recess **530A** may be provided over the entire or substantially the entire length of the first lateral surface-side external electrode **421A** along the lamination direction **T**. The first lateral surface-side recess **530A** is provided near the approximate center of the first lateral surface-side external electrode **421A** in the length direction **L**. The first lateral surface-side recess **530A** may communicate with either or both of the first main surface-side recess **510A** and the second main surface-side recess **520A**, or may not communicate with both.

[0114] As illustrated in FIG. 4, the second lateral surface-side external electrode **422A** of the first external electrode **40A** includes a second lateral surface-side recess **540A** recessed towards the multilayer body **10** side in the LW cross-sectional view.

[0115] The second lateral surface-side recess **540A** is provided on the surface of the second lateral surface-side external electrode **422A**.

[0116] The shape of the second lateral surface-side recess **540A** is a groove extending in the lamination direction **T** orthogonal or substantially orthogonal to the LW cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 4. The second lateral surface-side recess **540A** may be provided over the entire or substantially the entire length of the second lateral surface-side external electrode **422A** along the lamination direction **T**. The second lateral surface-side recess **540A** is provided near the approximate center of the second lateral surface-side external electrode **422A** in the length direction

L. The second lateral surface-side recess **540A** may communicate with either or both of the first main surface-side recess **510A** and the second main surface-side recess **520A**, or may not communicate with both.

[0117] As illustrated in FIG. 4, the first lateral surface-side external electrode **421B** of the second external electrode **40B** includes a first lateral surface-side recess **530B** recessed towards the multilayer body **10** side in the LW cross-sectional view. The first lateral surface-side recess **530B** is provided on the surface of the first lateral surface-side external electrode **421B**. The shape of the first lateral surface-side recess **530B** is a groove extending in the lamination direction **T** orthogonal or substantially orthogonal to the LW cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 4. The first lateral surface-side recess **530B** may be provided over the entire or substantially the entire length of the first lateral surface-side external electrode **421B** along the lamination direction **T**. The first lateral surface-side recess **530B** is provided near the approximate center of the first lateral surface-side external electrode **421B** in the length direction **L**. The first lateral surface-side recess **530B** may communicate with either or both of the first main surface-side recess **510B** and the second main surface-side recess **520B**, or may not communicate with both.

[0118] As illustrated in FIG. 4, the second lateral surface-side external electrode **422B** of the second external electrode **40B** includes a second lateral surface-side recess **540B** recessed towards the multilayer body **10** side in the LW cross-sectional view. The second lateral surface-side recess **540B** is provided on the surface of the second lateral surface-side external electrode **422B**. The shape of the second lateral surface-side recess **540B** is a groove extending in the lamination direction **T** orthogonal or substantially orthogonal to the LW cross section, i.e., in the direction perpendicular or substantially perpendicular to the paper surface of FIG. 4. The second lateral surface-side recess **540B** may be provided over the entire or substantially the entire length of the second lateral surface-side external electrode **422B** along the lamination direction **T**. The second lateral surface-side recess **540B** is provided near the approximate center of the second lateral surface-side external electrode **422B** in the length direction **L**. The second lateral surface-side recess **540B** may communicate with either or both of the first main surface-side recess **510B** and the second main surface-side recess **520B**, or may not communicate with both.

[0119] The first main surface-side external electrode **411A** and the second main surface-side external electrode **412A** of the first external electrode **40A**, as well as the first main surface-side external electrode **411B** and the second main surface-side external electrode **412B** of the second external electrode **40B**, share the same or substantially the same configuration. Similarly, the first lateral surface-side external electrode **421A** and the second lateral surface-side external electrode **422A** of the first external electrode **40A**, as well as the first lateral surface-side external electrode **421B** and the second lateral surface-side external electrode **422B** of the second external electrode **40B**, also share the same or substantially the same configuration as the four main surface-side external electrodes **411A**, **412A**, **411B**, and **412B**.

[0120] The first main surface-side recess **510A** and the second main surface-side recess **520A** of the first external

electrode 40A, as well as the first main surface-side recesses 510B and the second main surface-side recesses 520B of the second external electrode 40B, share the same or substantially the same configuration. Similarly, the first lateral surface-side recess 530A and the second lateral surface-side recess 540A of the first external electrode 40A, as well as the first lateral surface-side recess 530B and the second lateral surface-side recess 540B of the second external electrode 40B, also share the same or substantially the same configuration as the four main surface-side recesses 510A, 520A, 510B, and 520B.

[0121] Accordingly, the first main surface-side external electrode 411A and the first main surface-side recess 510A of the first external electrode 40A will be described below, representatively describing the four main surface-side external electrodes, the four main surface-side recesses, the four lateral surface-side external electrodes, and the four lateral surface-side recesses.

[0122] The first main surface-side external electrode 411A of the first external electrode 40A corresponds to the second main surface-side external electrode 412A, the first lateral surface-side external electrode 421A, and the second lateral surface-side external electrode 422A of the first external electrode 40A, as well as the first main surface-side external electrode 411B, the second main surface-side external electrode 412B, the first lateral surface-side external electrode 421B, and the second lateral surface-side external electrode 422B of the second external electrode 40B. The first main surface-side recess 510A of the first external electrode 40A corresponds to the second main surface-side recess 520A, the first lateral surface-side recess 530A, and the second lateral surface-side recess 540A of the first external electrode 40A, as well as the first main surface-side recesses 510B, the second main surface-side recesses 520B, the first lateral surface-side recess 530B, and the second lateral surface-side recess 540B of the second external electrode 40B.

[0123] The first base electrode layer 50A, the first conductive resin layer 60A, and the first plated layer 70A of the first external electrode 40A correspond to the second base electrode layer 50B, the second conductive resin layer 60B, and the second plated layer 70B of the second external electrode 40B, respectively. The first Ni plated layer 71A and the first Sn plated layer 72A of the first plated layer 70A of the first external electrode 40A correspond to the second Ni plated layer 71B and the second Sn plated layer 72B of the second plated layer 70B of the second external electrode 40B, respectively.

[0124] FIGS. 5A and 5B are both enlarged views of the portion indicated by V in FIG. 2, illustrating the LT cross-sectional view of the first main surface-side external electrode 411A of the first external electrode 40A. FIGS. 5A and 5B illustrate the XYZ orthogonal coordinate system similar to that in FIGS. 1 to 4. In FIGS. 5A and 5B, hatching is omitted to clearly illustrate symbols, leader lines, and dimension lines.

[0125] As illustrated in FIGS. 5A and 5B, the first main surface-side external electrode 411A of the first external electrode 40A includes the first main surface-side base electrode layer 511A and the first main surface-side conductive resin layer 611A on the first main surface TS1, and the first main surface-side plated layer 711A including the first Ni plated layer 71A and the first Sn plated layer 72A. The first main surface-side recess 510A includes the three layers

being recessed towards the multilayer body 10 side in the lamination direction T (the Z direction in FIGS. 5A and 5B), in which the three layers include the outermost first Sn plated layer 72A, the first Ni plated layer 71A beneath the first Sn plated layer 72A, and the first main surface-side conductive resin layer 611A beneath the first Ni plated layer 71A.

[0126] As illustrated in FIGS. 5A and 5B, the surface of the first main surface-side external electrode 411A includes the first main surface-side recess 510A, and also includes a first bulge 710 and a second bulge 720. The first bulge 710 is provided on the inner side of the first main surface-side recess 510A in the length direction L, i.e., on the central portion of the multilayer body 10 in the length direction L (away from the first end surface LS1 in the length direction L). The second bulge 720 is provided on the outer side of the first main surface-side recess 510A in the length direction L, i.e., on the outer side of the multilayer body 10 in the length direction L (closer to the first end surface LS1 in the length direction L). In other words, the first main surface-side external electrode 411A includes the first main surface-side recess 510A, as well as the first bulge 710 on the central portion of the multilayer body 10 in the length direction L, and the second bulge 720 on the end portion side of the multilayer body 10 in the length direction L, between which the first main surface-side recess 510A is interposed.

[0127] The reference number 700 in FIG. 5A represents a region of the first main surface-side recess 510A in the length direction L, in the present example embodiment. The region 700 of the first main surface-side recess 510A in the length direction L is based on the distance in the length direction L between a first midpoint 510m1, which connects a deepest portion 510d of the first main surface-side recess 510A to a vertex 710p of the first bulge 710, and a second midpoint 510m2, which connects the deepest portion 510d of the first main surface-side recess 510A to a vertex 720p of the second bulge 720. The deepest portion 510d of the first main surface-side recess 510A refers to the portion closest to the first main surface TS1 of the multilayer body 10 in the lamination direction T, in the first main surface-side recess 510A. The vertex 710p of the first bulge 710 is the point farthest from the first main surface TS1 of the multilayer body 10 in the lamination direction T, on the surface of the first bulge 710. The vertex 720p of the second bulge 720 is the point farthest from the first main surface TS1 of the multilayer body 10 in the lamination direction T, on the surface of the second bulge 720.

[0128] The distance between the vertex 710p of the first bulge 710 and the first main surface TS1 of the multilayer body 10 in the lamination direction T is the height 710H of the first bulge 710. The distance between the vertex 720p of the second bulge 720 and the first main surface TS1 of the multilayer body 10 in the lamination direction T is the height 720H of the second bulge 720.

[0129] In the present example embodiment, the height 710H of the first bulge 710 is preferably higher than the height 720H of the second bulge 720. The height 710H of the first bulge 710 and the height 720H of the second bulge 720 may be the same or different. In the cases of being different, the height 710H of the first bulge 710 may be higher or lower than the height 720H of the second bulge 720.

[0130] In the present example embodiment, the depth D of the first main surface-side recess 510A refers to the shortest

distance between the deepest portion **510d** and the line connecting the vertex **710p** of the first bulge **710** and the vertex **720p** of the second bulge **720**.

[0131] In the present example embodiment, the depth D of the first main surface-side recess **510A** is, for example, preferably between about 3 μm and about 10 μm inclusive.

[0132] In the present example embodiment, the depth D of the first main surface-side recess **510A** is preferably greater than the thickness of the Ni plated layer **71A** in the lamination direction T, in the first main surface-side external electrode **411A**.

[0133] As illustrated in FIG. 5A, in the present example embodiment, the distance L1 between the vertex **710p** of the first bulge **710** and the vertex **720p** of the second bulge **720** in the length direction L is, for example, preferably between about 100 μm and about 160 μm inclusive.

[0134] As illustrated in FIG. 5A, the distance L1 is preferably longer than the distance L2 between the inner end portion **411e** of the first main surface-side external electrode **411A** in the length direction L and the vertex **710p** of the first bulge **710** in the length direction L.

[0135] FIG. 2 illustrates the length L4 of the end surface-side outer layer portion LG (first end surface-side outer layer portion LG1, second end surface-side outer layer portion LG2) of the multilayer body **10** in the length direction L. FIG. 5A illustrates the length L4 of the first end surface-side outer layer portion LG1 in the length direction L. In the present example embodiment, the distance L1 between the vertex **710p** of the first bulge **710** and the vertex **720p** of the second bulge **720** in the length direction L is preferably longer than the length L4 of the first end surface-side outer layer portion LG1 of the multilayer body **10** in the length direction L.

[0136] The distance L1 is preferably greater than the maximum thickness of the first main surface-side external electrode **411A** in the lamination direction T. The distance L1 is preferably greater than the maximum thickness of the first main surface-side conductive resin layer **611A** in the lamination direction T. The distance L1 is preferably greater than the maximum thickness of the first main surface-side base electrode layer **511A** in the lamination direction T.

[0137] As illustrated in FIG. 5A, the distance L3 between the inner end portion **411e** of the first main surface-side external electrode **411A** in the length direction L and the deepest portion **510d** of the first main surface-side recess **510A** in the length direction L is preferably longer than the length L4 of the end surface-side outer layer portion LG of the multilayer body **10** in the length direction L. The distance L3 is, for example, preferably at least about 300 μm .

[0138] In the present example embodiment, the depth D of the first main surface-side recess **510A** is, for example, preferably between about 5% and about 15% inclusive of the maximum thickness of the first main surface-side external electrode **411A** in the lamination direction T.

[0139] As illustrated in FIG. 5A, in the present example embodiment, the distance L5 between the inner end portion **560a** of the first main surface-side base electrode layer **511A** and the deepest portion **510d** of the first main surface-side recess **510A** in the length direction L is, for example, preferably between about 15 μm and about 25 μm inclusive.

[0140] As illustrated in FIG. 5A, in the example embodiment, the distance L6 between the inner end portion **560a** of the first main surface-side base electrode layer **511A** and the

vertex **710p** of the first bulge **710** in the length direction L is, for example, preferably between about 40 μm and about 80 μm inclusive.

[0141] The first main surface-side recess **510A** includes the three layers being recessed towards the multilayer body **10** side in the lamination direction T, in which the three layers include the outermost first Sn plated layer **72A**, the first Ni plated layer **71A** beneath the first Sn plated layer **72A**, and the first main surface-side conductive resin layer **611A** beneath the first Ni plated layer **71A**. That is, the first main surface-side base electrode layer **511A** does not include a recess recessed towards the multilayer body **10** side in the lamination direction T.

[0142] As illustrated in FIG. 5B, in the LT cross-sectional view along the lamination direction T and the length direction L, the first main surface-side conductive resin layer **611A** includes a conductive resin layer recess **611c** that is recessed towards the multilayer body **10** side at the boundary interface **611k** with the first Ni plated layer **71A** of the first main surface-side plated layer **711A**. The conductive resin layer recess **611c** is provided substantially at the same position as the first main surface-side recess **510A** in the length direction L, corresponding to the first main surface-side recess **510A** in the length direction L. The region of the conductive resin layer recess **611c** in the length direction L corresponds to the region of the first main surface-side recess **510A** in the length direction L (indicated by the reference numeral **700** in FIG. 5A).

[0143] As illustrated in FIG. 5B, in the LT cross-sectional view, the deepest portion **611d** of the conductive resin layer recess **611c** is provided more inward than the inner end portion **560a** of the first main surface-side base electrode layer **511A**, i.e., towards the central portion of the multilayer body **10** in the length direction L. The deepest portion **611d** of the conductive resin layer recess **611c** refers to the portion closest to the first main surface TS1 of the multilayer body **10** in the lamination direction T, within the conductive resin layer recess **611c**.

[0144] The thickness **611t** of the first main surface-side conductive resin layer **611A** at the deepest portion **611d** of the conductive resin layer recess **611c** is, for example, preferably between about 5 μm and about 20 μm inclusive. The thickness **611t** is the distance between the deepest portion **611d** and the first main surface TS1 in the lamination direction T.

[0145] As illustrated in FIG. 5B, in the LT cross-sectional view, the first main surface-side conductive resin layer **611A** includes the conductive resin layer recess **611c**, as well as a first conductive resin layer bulge **810** and a second conductive resin layer bulge **820**. The first conductive resin layer bulge **810** is provided on the inner side of the conductive resin layer recess **611c** in the length direction L. The second conductive resin layer bulge **820** is provided on the outer side of the conductive resin layer recess **611c** in the length direction L. In other words, the first main surface-side conductive resin layer **611A** includes the conductive resin layer recess **611c**, as well as the first conductive resin layer bulge **810** on the central portion of the multilayer body **10** in the length direction L, and the second conductive resin layer bulge **820** on the end portion side of the multilayer body **10** in the length direction L, between which the conductive resin layer recess **611c** is interposed.

[0146] The surface of multilayer body **10** closest to, i.e., at the shortest distance from, the vertexes **810p** of the first

conductive resin layer bulge **810** and the vertex **820p** of the second conductive resin layer bulge **820**, is the first main surface TS1. The distance between the vertex **810p** of the first conductive resin layer bulge **810** and the first main surface TS1 of multilayer body **10** in the lamination direction T is the height **810H** of the first conductive resin layer bulge **810**. Similarly, the distance between the vertex **820p** of the second conductive resin layer bulge **820** and the first main surface TS1 of multilayer body **10** in the lamination direction T is the height **820H** of the second conductive resin layer bulge **820**.

[0147] In the present example embodiment, the height **810H** of the first conductive resin layer bulge **810** is preferably higher than the height **820H** of the second conductive resin layer bulge **820**. The height **810H** of the first conductive resin layer bulge **810** and the height **820H** of the second conductive resin layer bulge **820** may be the same or different. In the cases of being different, as described, the height **810H** of the first conductive resin layer bulge **810** may be higher or lower than the height **820H** of the second conductive resin layer bulge **820**.

[0148] In the present example embodiment, the height **810H** of the first conductive resin layer bulge **810** is, for example, preferably between about 15 μm and about 30 μm inclusive. On the other hand, the height **820H** of the second conductive resin layer bulge **820** is, for example, preferably between about 5 μm and about 20 μm inclusive.

[0149] The multilayer ceramic capacitor **1** of the present example embodiment is mounted on a board. Mounting to the board may include, for example, soldering, where the external electrodes **40** are joined to terminals on the board. When the first main surface-side external electrode **411A** is joined to the board by soldering, the flexure stress generated in the first main surface-side external electrode **411A**, concentrates particularly at the inner end portion **411e** of the first main surface-side external electrode **411A** or the inner end portion **611e** of the first main surface-side conductive resin layer **611A** as illustrated in FIG. 5B, and transmits as tensile stress to the multilayer body **10**, potentially causing cracks or the like in the multilayer body **10**. In the present example embodiment of the multilayer ceramic capacitor **1**, the first main surface-side external electrode **411A** includes the first main surface-side recess **510A**, and the first main surface-side conductive resin layer **611A** includes the conductive resin layer recess **611c**, thus dispersing the flexure stress to the first main surface-side recess **510A** and the conductive resin layer recess **611c** or around these recesses. This causes a mitigating effect on the flexure stress, thus reducing or preventing the occurrence of cracks in the multilayer body **10**. As a result, durability under harsh conditions is improved.

[0150] The dimensions such as the thickness of each layer of the first main surface-side external electrode **411A**, the depth of the first main surface-side recess **510A**, and the heights of the bulges are measured, for example, by the following method. Namely, the multilayer ceramic capacitor **1** is polished from either the first lateral surface WS1 or the second lateral surface WS2 to approximately half of the width dimension W. This exposes the LT cross section at the middle position of the multilayer ceramic capacitor **1** in the width direction W. Next, the dimensions in the LT cross section exposed by polishing are measured using a digital microscope.

[0151] Next, an example of a method of manufacturing the multilayer ceramic capacitor **1** according to the present example embodiment will be described. The method of manufacturing the multilayer ceramic capacitor **1** according to the present example embodiment is not limited, as long as the requirements described above are satisfied. However, a preferable example manufacturing method includes the following steps. The details of each step are described below.

[0152] A dielectric sheet for the dielectric layer **20** and a conductive paste for the internal electrode layer **30** are prepared. The dielectric sheet and the conductive paste for the internal electrode layer includes binders and solvents. The binders and solvents may be any known ones.

[0153] The conductive paste for the internal electrode layer **30** is printed in a predetermined pattern on the dielectric sheet, for example, by screen printing or gravure printing. As a result, a dielectric sheet with a pattern of the first internal electrode layer **31** and a dielectric sheet with a pattern of the second internal electrode layer **32** are prepared.

[0154] A predetermined number of dielectric sheets without printed patterns of internal electrode layer are stacked, thus forming a portion that becomes the first main surface-side outer layer portion **12A** on the first main surface TS1 side. On top of this, a dielectric sheet with printed patterns of the first internal electrode layer **31** and a dielectric sheet with printed patterns of the second internal electrode layer **32** are sequentially stacked, thus forming a portion that become the inner layer portion **11**. On top of the portion that become the inner layer portion **11**, a predetermined number of dielectric sheets without printed patterns of internal electrode layer are stacked, thus forming a portion that becomes the second main surface-side outer layer portion **12B** on the second main surface TS2 side. Thus, a multilayer sheet is produced.

[0155] The multilayer sheet is pressed in the lamination direction using, for example, hydrostatic pressing, thus producing a multilayer block.

[0156] The multilayer block is cut into a predetermined size, thus producing multilayer chips. At this time, the corners and edges of the multilayer chips may be rounded by barrel polishing.

[0157] The multilayer chips are fired to produce the multilayer body **10**. The firing temperature is, for example, preferably between about 900° C. and about 1400° C. inclusive, depending on the materials of the dielectric layer **20** and the internal electrode layer **30**.

[0158] A conductive paste to become the base electrode layer **50** is applied to both end surfaces of the multilayer body **10**. In the present example embodiment, the base electrode layer **50** is a fired layer. The conductive paste including glass components and metal components is applied to the multilayer body **10** by methods such as, for example, dipping. Subsequently, a firing process is performed, thus forming the base electrode layer **50**. The temperature during the firing process is, for example, preferably between about 700° C. and about 950° C. inclusive.

[0159] In the present example embodiment, dipping is conducted such that the first base electrode layer **50A** extends from the first end surface LS1 to a portion of the first main surface TS1 and the second main surface TS2. Similarly, dipping is conducted such that the second base electrode layer **50B** extends from the second end surface LS2 to a portion of the first main surface TS1 and the second main

surface TS2. In this case, dipping is preferably conducted simultaneously such that the first base electrode layer 50A extends to a portion of the first lateral surface WS1 and the second lateral surface WS2. Similarly, dipping is preferably conducted such that the second base electrode layer 50B extends to a portion of the first lateral surface WS1 and the second lateral surface WS2.

[0160] The pre-firing multilayer chips and the conductive paste applied to the multilayer chips may be simultaneously fired. In this case, the fired layers are preferably formed by, for example, firing a material including a ceramic material instead of glass components. In this case, as the ceramic material to be added, a ceramic material of the same type as the dielectric layer 20 is particularly preferably used. In this case, a conductive paste is applied to the pre-firing multilayer chips, and the multilayer chips as well as the conductive paste applied to the multilayer chips are simultaneously fired, thus forming the multilayer body 10 with the fired layers.

[0161] Next, the conductive resin layer 60 is formed. In the present example embodiment, the conductive resin layer 60 is formed on the surface of the base electrode layer 50 and a portion of the surface of the multilayer body 10.

[0162] First, a conductive resin paste is prepared, in which conductive fillers are dispersed within the thermosetting resin as the base resin that becomes the resin portion. The conductive resin paste is produced by, for example, stirring and mixing the thermosetting resin and the conductive fillers. Therefore, the conductive fillers are uniformly dispersed within the conductive resin paste. Here, the thermosetting resin is, for example, epoxy resin. The conductive filler is, for example, Ag metal powder.

[0163] Subsequently, the conductive resin paste is applied onto the base electrode layer 50 using, for example, a dipping method, and a thermal treatment is conducted at a temperature, for example, between about 200° C. and about 550° C. inclusive. This process thermally cures the resin portion, thus forming the conductive resin layer 60. The atmosphere during this heat treatment is, for example, preferably nitrogen (N₂). The oxygen concentration is preferably maintained at, for example, about 100 ppm or below to prevent the resin from scattering and the various metal components from oxidizing.

[0164] In the present example embodiment, dipping is conducted such that the first conductive resin layer 60A extends from the first end surface LS1 to a portion of the first main surface TS1 and the second main surface TS2. Similarly, dipping is conducted such that the second conductive resin layer 60B extends from the second end surface LS2 to a portion of the first main surface TS1 and the second main surface TS2. In this case, dipping is preferably conducted simultaneously such that the first conductive resin layer 60A extends to a portion of the first lateral surface WS1 and the second lateral surface WS2. Similarly, dipping is preferably conducted such that the second conductive resin layer 60B extends to a portion of the first lateral surface WS1 and the second lateral surface WS2.

[0165] Afterwards, the plated layer 70 is formed on the surface of the conductive resin layer 60. In the present example embodiment, for example, the Ni plated layer 71 and the Sn plated layer 72 are formed on the conductive resin layer 60. The Ni plated layer 71 and the Sn plated layer 72 are sequentially formed using an electroplating method. Barrel plating, for example, is a preferred method of plating.

[0166] The following may be an example of a method of forming the groove-shaped recesses in the main surface-side external electrodes and the lateral surface-side external electrodes of the external electrodes 40 as in the present example embodiment. FIGS. 6A to 6C schematically illustrate the steps of forming the base electrode layer 50 and the conductive resin layer 60 with this method. As illustrated in FIG. 6A, the base electrode paste 50P, which becomes the base electrode layer 50, is applied by dipping to the end portions of the multilayer body 10 in the length direction L, then the conductive resin paste 60P is applied by dipping, which becomes the conductive resin layer 60. Next, as illustrated in FIG. 6B, the multilayer body 10 is passed between a pair of rod-shaped tools 90 facing each other. The passage direction herein is the direction perpendicular or substantially perpendicular to the paper surface of FIG. 6B. As a result, as illustrated in FIG. 6C, groove-shaped recesses G are formed on both sides of the conductive resin paste 60P that is the conductive resin layer 60, at the tips of the pair of rod-shaped tools 90. These recesses G become the first main surface-side recess 510A, the second main surface-side recess 520A, the first lateral surface-side recess 530A, the second lateral surface-side recess 540A, the first main surface-side recess 510B, the second main surface-side recess 520B, the first lateral surface-side recess 530B, and the second lateral surface-side recess 540B. Thereafter, the Ni plated layer 71 and the Sn plated layer 72 are formed on the conductive resin layer 60.

[0167] The recesses can also be formed by appropriately adjusting the viscosity of the base electrode paste 50P and the conductive resin paste 60P, or by innovating the dipping method. The multilayer ceramic capacitor 1 is manufactured through the manufacturing steps described above.

[0168] The configurations of the multilayer ceramic capacitor 1 is not limited to those illustrated in FIGS. 1 to 4B. For example, the multilayer ceramic capacitor 1 may include a two-portion structure, a three-portion structure, or a four-portion structure as illustrated in FIGS. 7A to 7C.

[0169] The multilayer ceramic capacitor 1 illustrated in FIG. 7A includes a two-portion structure, including a floating internal electrode layer 35 as a floating inner conductive layer that does not extend to either the first end surface LS1 or the second end surface LS2, in addition to the first internal electrode layer 33 and the second internal electrode layer 34 as the internal electrode layer 30.

[0170] The multilayer ceramic capacitor 1 illustrated in FIG. 7B includes a three-portion structure, including a first floating internal electrode layer 35A and a second floating internal electrode layer 35B, as the floating internal electrode layer 35.

[0171] The multilayer ceramic capacitor 1 illustrated in FIG. 7C includes a four-portion structure, including the first floating internal electrode layer 35A, the second floating internal electrode layer 35B, and a third floating internal electrode layer 35C, as the floating internal electrode layer 35.

[0172] The multilayer ceramic capacitor 1 can be structured with a plurality of divided counter electrode portions by providing the floating internal electrode layers 35 as the internal electrode layer 30. As a result, a plurality of capacitor components are provided between the counter internal electrode layers 30, and the capacitor components are connected in series. Therefore, the voltage applied to each capacitor component is reduced, thus achieving high with-

stand voltage of the multilayer ceramic capacitor **1**. The multilayer ceramic capacitor **1** in the present example embodiment may include a multi-portion structure of four or more portions.

[0173] In the multilayer ceramic capacitors **1** with the structures illustrated in FIGS. 7A to 7C, as in the case of the above-described example embodiments, both of the first external electrode **40A** and the second external electrode **40B** include the main surface-side external electrodes that include the main surface-side recesses. Although not illustrated, the conductive resin layers defining each main surface-side external electrode include the conductive resin layer recesses that are recessed towards a side of the multilayer body at a boundary interface with the main surface-side plated layer.

[0174] In the multilayer ceramic capacitors **1** with the structures illustrated in FIGS. 7A to 7C, as in the case of the above-described example embodiments, both of the first external electrode **40A** and the second external electrode **40B** include the lateral surface-side external electrodes that include the lateral surface-side recesses. Although not illustrated, the conductive resin layers defining each lateral surface-side external electrode include the conductive resin layer recesses that are recessed towards the side of the multilayer body at the boundary interface with the lateral surface-side plated layer.

[0175] In particular, the multilayer ceramic capacitors **1** with the structures such as the two-portion structure, the three-portion structure, and the four-portion structure including the floating internal electrode layer **35** illustrated in FIGS. 7A to 7C are effective for use under high voltage. However, compressive stress is preferably applied to the multilayer body **10** as an electrostrictive countermeasure under high voltage, and in order to achieve this, the plating thickness of the external electrodes on the main surfaces and the lateral surfaces of the multilayer body **10** is increased. However, this can lead to a problem where the flexural resistance deteriorates due to increased tensile stress at the inner end portion **611e** of the external electrode **40** and the inner end portion **611e** of the conductive resin layer **60A**, as illustrated in FIG. 5B. However, as in the above-described example embodiments, for example, the recesses (the first main surface-side recess and the second main surface-side recess) are provided in the main surface-side external electrodes, and the conductive resin layer recesses are provided, thus improving the flexural resistance, and reducing or preventing the occurrence of cracks in the multilayer body **10**.

[0176] The multilayer ceramic capacitor **1** according to the example embodiments can achieve the following advantageous effects.

[0177] (1) A multilayer ceramic capacitor **1** according to an example embodiment includes the multilayer body **10** that includes the dielectric layers **20** as the plurality of ceramic layers, and the internal electrode layers **30** as the plurality of inner conductive layers alternately stacked in the lamination direction **T** as the height direction. The multilayer body **10** also includes the first main surface **TS1** and the second main surface **TS2** on opposite sides in the lamination direction **T**, the first end surface **LS1** and the second end surface **LS2** on opposite sides in the length direction **L** orthogonal or substantially orthogonal to the lamination direction **T**, and the first lateral surface **WS1** and the second lateral

surface **WS2** on opposite sides in the width direction **W** orthogonal or substantially orthogonal to both the lamination direction **T** and the length direction **L**. The multilayer body **10** also includes the pair of external electrodes **40** spaced apart from each other at the end portions of the multilayer body **10** in the length direction **L**. The internal electrode layers **30** include the first internal electrode layer **31** as the first inner conductive layer extending to the first end surface **LS1**, and the second internal electrode layer **32** as the second inner conductive layer extending to the second end surface **LS2**. The external electrodes **40** include the first main surface-side external electrode **411A** and the second main surface-side external electrode **412A**, as well as the first main surface-side external electrode **411B** and the second main surface-side external electrode **412B**, on the first main surface **TS1** and the second main surface **TS2**, respectively. The first main surface-side external electrode **411A** and the second main surface-side external electrode **412A**, as well as the first main surface-side external electrode **411B** and the second main surface-side external electrode **412B** include the first main surface-side base electrode layer **511A** and the second main surface-side base electrode layer **512A**, as well as the first main surface-side base electrode layer **511B** and the second main surface-side base electrode layer **512B**, as the main surface-side base electrode layers, the first main surface-side conductive resin layer **611A** and the second main surface-side conductive resin layer **612A**, as well as the first main surface-side conductive resin layer **611B** and the second main surface-side conductive resin layer **612B** above the main surface-side base electrode layers, and the first main surface-side plated layer (main surface-side plated layer) **711A** and the second main surface-side plated layer **712A**, as well as the first main surface-side plated layer **711B** and the second main surface-side plated layer **712B**, as the main surface-side plated layer above the main surface-side conductive resin layers, respectively. Each main surface-side conductive resin layer includes the conductive resin layer recess **611c** that is recessed towards the multilayer body **10** side at the boundary interface **611k** with the main surface-side plated layer, in the cross-sectional view along the lamination direction **T** and the length direction **L**.

[0178] When the multilayer ceramic capacitor **1** of the present example embodiment is mounted on a board by soldering, the flexure stress generated in the first main surface-side external electrode **411A** does not concentrate at the inner end portion **611e** of the first main surface-side conductive resin layer **611A** but disperses to or around the conductive resin layer recess **611**. This causes a mitigating effect on the flexure stress, thus reducing or preventing the occurrence of cracks in the multilayer body **10**.

[0179] (2) In a multilayer ceramic capacitor **1** of an example embodiment, the deepest portion **611d** of the conductive resin layer recess **611c** is preferably provided closer to the central portion of the multilayer body **10** in the length direction **L**, than the inner end portion **560a** of the first main surface-side base electrode layer **511A** in the length direction **L**, in the cross-sectional view along the lamination direction **T** and the length direction **L**.

[0180] This causes a mitigating effect on the flexure stress, thus reducing or preventing the occurrence of cracks in the multilayer body 10.

[0181] (3) In a multilayer ceramic capacitor 1 of an example embodiment, in the cross-sectional view along the lamination direction T and the length direction L, the first main surface-side conductive resin layer 611A includes the first conductive resin layer bulge 810 on the central portion of the multilayer body 10 in the length direction L, and the second conductive resin layer bulge 820 on the end portion side of the multilayer body 10 in the length direction L, between which the conductive resin layer recess 611c is interposed. The height 810H of the first conductive resin layer bulge 810, which is the shortest distance from the surface of the multilayer body 10 to the vertex 810p of the first conductive resin layer bulge 810, is preferably higher than the height 820H of the second conductive resin layer bulge 820, which is the shortest distance from the surface of the multilayer body 10 to the vertex 820p of the second conductive resin layer bulge 820.

[0182] This causes a mitigating effect on the flexure stress, thus reducing or preventing the occurrence of cracks in the multilayer body 10.

[0183] In an example embodiment of the multilayer ceramic capacitor 1, each of the first external electrode 40A and the second external electrode 40B may include a lateral surface-side external electrode, which may also include a conductive resin layer including a conductive resin layer recess, as in the case of the main surface-side external electrodes.

[0184] Thus, a multilayer ceramic capacitor 1 according to an example embodiment includes the multilayer body 10 that includes the dielectric layers 20 as the plurality of ceramic layers, and the internal electrode layers 30 as the plurality of inner conductive layers alternately stacked in the lamination direction T as the height direction. The multilayer body 10 also includes the first main surface TS1 and the second main surface TS2 on opposite sides in the lamination direction T, the first end surface LS1 and the second end surface LS2 on opposite sides in the length direction L orthogonal or substantially orthogonal to the lamination direction T, and the first lateral surface WS1 and the second lateral surface WS2 on opposite sides in the width direction W orthogonal or substantially orthogonal to both the lamination direction T and the length direction L. The multilayer body 10 also includes the pair of external electrodes 40 spaced apart from each other at the end portions of the multilayer body 10 in the length direction L. The internal electrode layers 30 include the first internal electrode layer 31 as the first inner conductive layer extending to the first end surface LS1, and the second internal electrode layer 32 as the second inner conductive layer extending to the second end surface LS2. The external electrodes 40 include a lateral surface-side external electrode on at least one of the first lateral surface WS1 or the second lateral surface WS2. The lateral surface-side external electrode includes a lateral surface-side base electrode layer, a lateral surface-side conductive resin layer above the lateral surface-side base electrode layer, and a lateral surface-side plated layer above the lateral surface-side conductive resin layer. The lateral surface-side conductive resin layer includes a conductive resin layer recess recessed towards a side of the multilayer body at a boundary interface with the

lateral surface-side plated layer, in a cross-sectional view along the lamination direction T and the length direction L.

[0185] The present invention is not limited to the configurations of the example embodiments and can be appropriately modified and applied within the scope of the present invention.

[0186] Combinations of two or more of any individual configurations described in the example embodiments are also included in the present invention.

[0187] For example, the multilayer ceramic capacitor 1 may be of a two-terminal multilayer ceramic capacitor including two external electrodes or a multi-terminal multilayer ceramic capacitor including a plurality of external electrodes.

[0188] In the example embodiments described above, the multilayer ceramic capacitor using dielectric ceramics has been described as an example of the multilayer ceramic electronic component. However, the multilayer ceramic electronic component disclosed herein is not limited to this, and various multilayer ceramic electronic components such as, for example, piezoelectric components using piezoelectric ceramics, thermistors using semiconductor ceramics, and inductors using magnetic ceramics can also be applied. Examples of piezoelectric ceramics may include PZT (lead zirconate titanate) ceramics, examples of semiconductor ceramics may include spinel ceramics, and examples of magnetic ceramics may include ferrites.

[0189] While example embodiments of the present invention have been described above, it is to be understood that variations and modifications will be apparent to those skilled in the art without departing from the scope and spirit of the present invention. The scope of the present invention, therefore, is to be determined solely by the following claims.

What is claimed is:

1. A multilayer ceramic electronic component, comprising:

- a multilayer body that includes a plurality of ceramic layers and a plurality of inner conductive layers stacked alternately in a height direction, a first main surface and a second main surface on opposite sides in the height direction, a first end surface and a second end surface on opposite sides in a length direction orthogonal or substantially orthogonal to the height direction, and a first lateral surface and a second lateral surface on opposite sides in a width direction orthogonal or substantially orthogonal to both the height direction and the length direction; and

- a pair of external electrodes spaced apart from each other at both end portions of the multilayer body in the length direction; wherein

the plurality of inner conductive layers include:

- a first inner conductive layer extending to the first end surface; and

- a second inner conductive layer extending to the second end surface;

the pair of external electrodes include:

- a main surface-side external electrode on at least one of the first main surface or the second main surface;

the main surface-side external electrode includes:

- a main surface-side base electrode layer;

- a main surface-side conductive resin layer above the main surface-side base electrode layer; and

- a main surface-side plated layer above the main surface-side conductive resin layer; and

in a cross-sectional view along the height direction and the length direction, the main surface-side conductive resin layer includes a conductive resin layer recess recessed toward a side of the multilayer body at a boundary interface with the main surface-side plated layer.

2. The multilayer ceramic electronic component according to claim 1, wherein, in the cross-sectional view along the height direction and the length direction, a deepest portion of the conductive resin layer recess is closer to a central portion of the multilayer body in the length direction than an inner end portion of the main surface-side base electrode layer in the length direction.

3. The multilayer ceramic electronic component according to claim 1, wherein

in the cross-sectional view along the height direction and the length direction, the main surface-side conductive resin layer includes a first conductive resin layer bulge on a central portion of the multilayer body in the length direction, and a second conductive resin layer bulge on an end portion side of the multilayer body in the length direction, between which the conductive resin layer recess is interposed;

a height of the first conductive resin layer bulge, being a shortest distance from a surface of the multilayer body to a vertex of the first conductive resin layer bulge, is higher than a height of the second conductive resin layer bulge, being a shortest distance from a surface of the multilayer body to a vertex of the second conductive resin layer bulge.

4. The multilayer ceramic electronic component according to claim 1, wherein

a dimension of the multilayer body in the length direction L is between about 0.2 mm and about 10 mm inclusive;

a dimension of the multilayer body in the height direction is between about 0.1 mm and about 10 mm inclusive; and

a dimension of the multilayer body in the width direction is between about 0.1 mm and about 10 mm inclusive.

5. The multilayer ceramic electronic component according to claim 1, wherein the multilayer body includes:

an inner layer portion including some of the plurality of ceramic layers and some of the plurality of inner conductive layers; and

first and second main surface-side outer layer portions with the inner layer portion interposed therebetween.

6. The multilayer ceramic electronic component according to claim 1, wherein each of the plurality of ceramic layers includes BaTiO_3 , CaTiO_3 , SrTiO_3 , or CaZrO_3 as a main component.

7. The multilayer ceramic electronic component according to claim 6, wherein each of the plurality of ceramic

layers includes a Mn compound, a Fe compound, a Cr compound, a Co compound, or a Ni compound as an accessory component.

8. The multilayer ceramic electronic component according to claim 1, wherein a thickness of each of the plurality of ceramic layers is between about 0.5 μm and about 30 μm inclusive.

9. The multilayer ceramic electronic component according to claim 1, wherein a number of the plurality of ceramic layers is between 10 and 1500 inclusive.

10. The multilayer ceramic electronic component according to claim 1, wherein each of the plurality of inner conductive layers includes Ni, Cu, Ag, Pd, or Au, or alloys including at least one of Ni, Cu, Ag, Pd, or Au.

11. The multilayer ceramic electronic component according to claim 1, wherein a thickness of each of the plurality of inner conductive layers is between about 0.2 μm and about 2.0 μm inclusive.

12. The multilayer ceramic electronic component according to claim 1, wherein a number of the plurality of inner conductive layers is between 10 and 1500 inclusive.

13. The multilayer ceramic electronic component according to claim 1, wherein the main surface-side plated layer includes a Ni plated layer, and a Sn plated layer on the Ni plated layer.

14. The multilayer ceramic electronic component according to claim 1, wherein the main surface-side base electrode layer includes a metal component and at least one of a glass component and a ceramic component.

15. The multilayer ceramic electronic component according to claim 14, wherein the metal component includes at least one of Cu, Ni, Ag, Pd, Ag—Pd alloy, or Au.

16. The multilayer ceramic electronic component according to claim 14, wherein the glass component includes at least one of B, Si, Ba, Mg, Al, or Li.

17. The multilayer ceramic electronic component according to claim 14, wherein the ceramic component includes at least one of BaTiO_3 , CaTiO_3 , $(\text{Ba}, \text{Ca})\text{TiO}_3$, SrTiO_3 , or CaZrO_3 .

18. The multilayer ceramic electronic component according to claim 1, wherein a thickness of the main surface-side base electrode layer is between about 2 μm and about 220 μm inclusive.

19. The multilayer ceramic electronic component according to claim 1, wherein the main surface-side conductive resin layer includes a resin portion including resin components, and conductive filler particles dispersed within the resin portion.

20. The multilayer ceramic electronic component according to claim 1, wherein a thickness of the main surface-side conductive resin layer is between about 5 μm and about 200 μm inclusive.

* * * * *