

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279282

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

Otto, IV; Ivo et al.

IN SITU REMOVABLE BLOCKING LAYER FORMATION

Abstract

A method of etching a target material of a substrate includes selectively forming a blocking layer on an oxygen-containing material using ammonia gas and at least one fluorine-containing gas, etching the target material using an etchant gas, and removing the blocking layer from the oxygen-containing material by exposing the vertical stack to a temperature of at least 80° C. The substrate also includes a vertical stack of layers of a first material suspended between structures of a second material. The oxygen-containing material covers surfaces of the second material in openings between the layers of the first material. The blocking layer inhibits diffusion of the etchant gas into the second material.

Inventors: Otto, IV; Ivo (Albany, NY), Hajibabaeinajafabadi; Hamed (Albany, NY), Rednor; Matthew (Albany, NY), Kanaki; Toshiki (Albany, NY)

Applicant: Tokyo Electron Limited (Tokyo, JP)

Family ID: 96880468

Appl. No.: 18/591695

Filed: February 29, 2024

Publication Classification

Int. Cl.: H01L21/311 (20060101); H01L21/02 (20060101); H01L29/66 (20060101)

U.S. Cl.:

CPC H01L21/31116 (20130101); H01L21/02636 (20130101); H10D64/018 (20250101);

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates generally to etching processes, and, in particular embodiments, to systems and methods for etching processes that include in situ formation of a removable blocking layer.

BACKGROUND

[0002] Microelectronic device fabrication typically involves a series of manufacturing techniques that include formation, patterning, and removal of a number of layers of material on a substrate. Etch masks may be formed (e.g., deposited, grown, patterned) to protect regions of the substrate and allow for pattern transfer via etching. Wet or dry etching processes may be used, and the directionality of the etch may be isotropic or anisotropic. Isotropic etching processes are often used to etch laterally (e.g., underneath or between materials).

[0003] Etching processes are often tailored to be selective to a specific material or class of materials. For this reason, structures of similar material composition can be etched at the same time with a particular pattern of protective structures (e.g., a single mask). However, simultaneous etching of structures with differing dimensionality can be difficult without introducing additional process steps to protect each type or structure. Differences in dimensionality that may introduce uneven etching may be critical dimension (CD), aspect ratio, feature density, height, length, shape, and others. The features that etch faster, such as the smaller structures, may expose materials sensitive to the etchant that are not the target of the etch before the larger structures have reached the etching endpoint. That is, undesirable damage due to overetching may occur to structures underlying or adjacent to etch targets that reach the endpoint faster while desirable etching continues on other structures.

[0004] Additional process steps, such as additional mask formation steps, decrease throughput. Further, more process steps can also decrease yield due to the compounding of defects at each step. Damage from overetching is also a consequence of undesirably low overetch margin (i.e., the amount of overetching that a structure can endure without impacting device yield or performance). Therefore, improved etching processes that allow etching of structures of difference dimensionality without additional process steps by improving overetch margin may be desirable.

SUMMARY

[0005] In accordance with an embodiment of the invention, a method of etching a target material of a substrate includes selectively forming a blocking layer on an oxygen-containing material using ammonia gas and at least one fluorine-containing gas, etching the target material using an etchant gas, and removing the blocking layer from the oxygen-containing material by exposing the vertical stack to a temperature of at least 80° C. The substrate also includes a vertical stack of layers of a first material suspended between structures of a second material. The oxygen-containing material covers surfaces of the second material in openings between the layers of the first material. The blocking layer inhibits diffusion of the etchant gas into the second material.

[0006] In accordance with another embodiment of the invention, a channel release method for longer channel devices of a substrate that also includes shorter channel devices includes performing the following steps without breaking vacuum: selectively forming a blocking layer on inner spacers of the shorter channel devices; etching silicon germanium (SiGe) layers of the longer channel devices using an etchant gas; and removing the blocking layer from the inner spacers by exposing the shorter channel devices to a temperature of at least 80° C. The inner spacers cover surfaces of SiGe source/drain structures in openings between silicon (Si) layers suspended between the SiGe source/drain structures. The blocking layer inhibits diffusion of the etchant gas into the SiGe source/drain structures.

[0007] In accordance with still another embodiment of the invention, a system includes a processing chamber; a substrate support configured to support a substrate within the processing chamber, one or more valves configured to fluidically couple a blocking gas and an etchant gas to

the processing chamber, and a controller operatively coupled to the one or more valves. The substrate includes a target material and a vertical stack of layers of a first material suspended between structures of a second material. The controller includes a processor and a non-transitory computer-readable medium storing a program including instructions that, when executed by the processor, perform a method without breaking a vacuum environment of the system. The method includes selectively forming, in the processing chamber, a blocking layer on an inner spacer material covering surfaces of the second material in openings between the layers of the first material using the blocking gas, etching, in the processing chamber, the target material using the etchant gas, and removing the blocking layer from the inner spacer material. The blocking layer inhibits diffusion of the etchant gas into the second material.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] For a more complete understanding of the present invention, and the advantages thereof, reference is now made to the following descriptions taken in conjunction with the accompanying drawings, in which:

[0009] FIGS. 1A-1D illustrate an example etching process that uses a blocking layer to inhibit diffusion while etching a target material, where FIG. 1A shows an initial state of a substrate with inner spacers in openings of a vertical stack of layers, FIG. 1B shows a selective formation step of forming a blocking layer on the inner spacers, FIG. 1C shows an etch step of etching the target material while the blocking layer inhibits diffusion, and FIG. 1D shows a removal step of removing the blocking layer in accordance with embodiments of the invention;

[0010] FIGS. 2A-2C illustrate another example etching process that uses a blocking layer to inhibit diffusion while etching a target material, where FIG. 2A shows an initial state of a substrate with inner spacers in openings of a vertical stack of layers, FIG. 2B shows an optional pretreatment step that modifies surfaces of the inner spacers, and FIG. 2C shows a combined step of selectively forming the blocking layer on the inner spacers while etching the target material in accordance with embodiments of the invention;

[0011] FIG. 3 illustrates an example system that may be used to perform one or more steps of the etching processes without breaking vacuum in accordance with embodiments of the invention;

[0012] FIG. 4 illustrates another example system that may be used to perform one or more steps of the etching processes without breaking vacuum in accordance with embodiments of the invention;

[0013] FIG. 5 illustrates an example method etching a target material of a substrate that also includes a vertical stack of layers of a first material suspended between structures of a second material in accordance with embodiments of the invention; and

[0014] FIG. 6 illustrates a conventional channel release process resulting in undesirable damage to source/drain structures of shorter channel devices.

[0015] Corresponding numerals and symbols in the different figures generally refer to corresponding parts unless otherwise indicated. The figures are drawn to clearly illustrate the relevant aspects of the embodiments and are not necessarily drawn to scale. The edges of features drawn in the figures do not necessarily indicate the termination of the extent of the feature.

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0016] The making and using of various embodiments are discussed in detail below. It should be appreciated, however, that the various embodiments described herein are applicable in a wide variety of specific contexts. The specific embodiments discussed are merely illustrative of specific ways to make and use various embodiments, and should not be construed in a limited scope. Unless specified otherwise, the expressions “around”, “approximately”, and “substantially” signify within 10%, and preferably within 5% of the given value or, such as in the case of substantially zero, less

than 10% and preferably less than 5% of a comparable quantity.

[0017] Microelectronic device fabrication often utilizes several etching processes to modify structures on a substrate. For example, isotropic etching processes are often used to etch laterally (e.g., underneath or between materials). One application where isotropic etching processes are used is when etching three-dimensional structures. Various three-dimensional devices, such as gate-all-around (GAA) devices utilize vertical stacks of two or more types of materials during the fabrication process. One such vertical stack of layers (e.g., alternating silicon (Si) and silicon germanium (SiGe) layer) is used in GAA field-effect transistor (FET) devices to form multibridge channels by etching away one type of layer to suspend the remaining layers (i.e., a channel release process).

[0018] During the channel release process, the sacrificial layers between the channel layers may be removed. The suspended channel layers may extend between source/drain structures. Damage to the source/drain structures during the channel release process is undesirable because it can negatively impact device performance. In some cases, the entire source/drain structure may be removed. Because the channel length between devices may vary on a single substrate, the sacrificial layers may be completely etched away in shorter channel devices while longer channel devices still need to be etched to fully release the channel layers. For this reason, overetch margin for the shorter channel devices may influence the ability to etch both the shorter channel structures and the longer channel structures during the same etching process.

[0019] Inner spacers may be formed between the sacrificial layers and the source/drain structures. The inner structures may not be significantly affected by the etchant during the channel release process (e.g., functioning as a source of increased overetch margin for the etching process). However, the inner spacers may still allow diffusion of the etchant through to source/drain structures given sufficient overetch time. Specifically, the additional etch time required to etch longer channel structures may be more (e.g., much more) than the overetch protection afforded by the inner spacers.

[0020] FIG. 6 illustrates a conventional channel release process **699** resulting in undesirable damage to source/drain structures of shorter channel devices. In this specific example, during the conventional channel release process **699**, a substrate **683** that includes both shorter channel devices **685** and longer channel devices **694** may be etched to remove sacrificial layers from between Si short channel layers **691** and Si long channel layers **696** to form openings **693** and openings **698**, respectively. The Si short channel layers **691** are then suspended between SiGe source/drain structures **690** and separated by inner spacers **692**, while the Si long channel layers **696** are suspended between SiGe source/drain structures **695** and separated by inner spacers **697**.

[0021] Yet, despite the presence of the inner spacers **692**, the increased etch timer caused by the difference in channel length results in undesirable short channel SiGe source/drain damage **679**. That is, even though the etchant gas does not negatively interact with the inner spacers **692**, the etchant gas diffuses through the inner spacers **692** and etches away the SiGe source/drain structures **690**. Without modification, the conventional channel release process **699** is undesirably limited by the overetch margin of the shorter channel devices **685**.

[0022] Therefore, an improved etching process that increases the overetch margin for structures with smaller dimensionality while avoiding undesirable consequences, (e.g., decreased throughput, device performance, yield, process performance, etc.) are desirable both in this specific case as well as in any case where an etchant gas may diffuse through a layer to damage structures before the etching process has reached the endpoint.

[0023] In accordance with embodiments herein described, the invention proposes the selective formation of a blocking layer as part of an etching process. The blocking layer is formed on structures of a certain material composition to protect against overetching. The formation of the blocking layer may be fully integrated into the etching process, such as by both etching a target material and forming the blocking layer in situ in the same chamber. The blocking layer may be

configured to inhibit or prevent undesirable diffusion of an etchant gas into nearby materials. As an example of one specific application, the blocking layer may be selectively formed on inner spacer structures of a vertical stack of channel layers to protect source/drain structures from damage while etching other regions on the same substrate (e.g., sacrificial layers for channel release of longer channel devices). After the etching of the target material reaches a desired endpoint, the blocking layer is removed.

[0024] Embodiments of the invention apparent from the description herein may have various advantages over conventional etching processes. For example, damage to certain structures (e.g., source/drain structures) may be decreased or prevented without negatively impacting process performance, such as channel release process performance, thereby increasing device yield and/or device performance. The mitigation of structural damage may be advantageously reflected in increased overetch margin compared to conventional etching processes, reducing process marginality and improving device yield. In the specific application of channel release processes for substrates that include both shorter channel devices and longer channel devices, the increased overetch margin of the embodiment etching processes may have the advantage of preventing damage to the shorter channel devices (which have already completed the channel release) while the channel release etch is continued on the longer channel devices.

[0025] A further advantage of the embodiment etching processes may be to achieve the benefits of the blocking layer and then fully remove the blocking layer without impacting the material composition of the remaining structures. That is, the blocking layer may be removed to expose pristine material surfaces (no persisting modification of the underlying materials). For example, when the blocking layer is formed on structures of a certain material, the atomic concentrations of the certain material before formation and after removal of the blocking layer may advantageously remain the same to within 1% (or even lower).

[0026] Embodiments provided below describe various etching processes, and in particular, systems and methods for etching processes that include in situ formation of a removable blocking layer. The following description describes the embodiments. FIGS. 1A-1D are used to describe an example etching process. Another example etching process is described using FIGS. 2A-2C. Two example systems that may be used to perform etching processes that include in situ formation of a removable blocking layer are described using FIGS. 3 and 4. An example method of etching a target material is described using FIG. 5.

[0027] FIGS. 1A-1D illustrate an example etching process that uses a blocking layer to inhibit diffusion while etching a target material, where FIG. 1A shows an initial state of a substrate with inner spacers in openings of a vertical stack of layers, FIG. 1B shows a selective formation step of forming a blocking layer on the inner spacers, FIG. 1C shows an etch step of etching the target material while the blocking layer inhibits diffusion, and FIG. 1D shows a removal step of removing the blocking layer in accordance with embodiments of the invention. While the etching process described using FIGS. 1A-1D gives specific structures and materials in order to provide context, as mentioned throughout the disclosure, the etching process may also apply to other structures and materials.

[0028] Referring to FIG. 1A, an initial state **108** of a substrate **110** of the etching process **100** includes shorter channel devices **120** and longer channel devices **130**. The shorter channel devices **120** have a first vertical stack of layers **124** (e.g., a suspended channel structure) with short channel layers **123** suspended between structures **122** of a second material **121** (e.g., source/drain structures). The short channel layers **123** are formed of a first material **125** and are separated by inner spacers **126** disposed in openings **128** between the short channel layers **123**.

[0029] Similarly, the longer channel devices **130** may have a second vertical stack of layers **134** (e.g., a channel structure with a longer channel length than the shorter channel devices) disposed between structures **132** of the second material **121** (or of a different material in other embodiments). The second vertical stack of layers **134** includes long channel layers **133** of the first

material **125** (or of a different material) separated by inner spacers **136** and sacrificial layers **137** that are formed of a target material **135**.

[0030] The substrate **110** may be any suitable substrate, such as an insulating, conducting, or semiconducting substrate with one or more layers disposed thereon. One example category of possible substrates would be one of the many types of semiconductor wafer (silicon, silicon-on-insulator, germanium, gallium arsenide, etc.). The substrate **110** may include any manner of microelectronic devices, such as semiconductor devices. Additionally, the substrate **110** may be in an intermediate stage of fabrication to form such devices. For example, various electronic components may be included on the substrate **110** such as active components like transistors, gated diodes, and silicon-controlled rectifiers (SCRs), and passive components like resistors, capacitors, inductors, and diodes. The components may be configured to perform tasks like amplification, regulation, and signal modulation by selecting various materials, structures, and arrangements of the components. The components may be arranged in specialized circuits, some of which include memory circuits, such as random access memory (RAM), read-only memory (ROM), and flash memory, digital logic circuits including logic gates, multiplexers, decoders and encoders, flip-flops, and registers, and analog circuits such as signal processors, filters, sensors, and the like. In various embodiments, the substrate **110** is or will be an integrated circuit (IC), ranging from largescale ICs, such as a microcontroller or microprocessor, so smaller, specialized ICs.

[0031] The shorter channel devices **120** may be any type of device or intermediate structure (for simplicity reasons, the shorter channel devices **120** are called “devices” even though the structures being referenced can be and often are intermediate structures that will be part of or used to form part of the completed device). In the specific example of the etching process **100**, the shorter channel devices **120** include the first vertical stack of layers **124**, which may be part of a three-dimensional device (e.g., a multilayer device), such as a GAA transistor like a GAA FET. The doping type of the device may also vary, including p-type (e.g., pFET), n-type (e.g., nFET), mixed type, etc.

[0032] The longer channel devices **130** may also be any type of device or intermediate structure that includes the target material **135** of the etching process **100**. In this specific example, the longer channel devices **130** include the second vertical stack of layers **134** (a similar structure as the shorter channel devices **120**), but the long channel layers **133** have a longer length than the short channel layers **123** of the shorter channel devices **120**. The size of the length difference may vary, but is on the order of tens of nanometers in one embodiment. The absolute length of the long channel layers **133** may also vary. For example, the channel length of the longer channel devices **130** may be at least about 50 nm, but may also be longer, such as at least about 100 nm, at least about 200 nm, or even longer.

[0033] The short channel layers **123** and the long channel layers **133** may be made from the same material (as shown) or may be different materials. In various embodiments, the first material **125** of the short channel layers **123** and the long channel layers **133** contains Si, and the first material **125** is Si in one embodiment (doped silicon channel layers, for example). The structures **122** and the structures **132** may be source/drain structures for their respective channel structures. In various embodiments, the second material **121** of the structures **122** and the structures **132** contains Si, and the second material **121** is SiGe in one embodiment. While the material of the structures **122** and the structures **132** may be different, they are the same material in one embodiment.

[0034] The inner spacers **126** may be formed from a dielectric material, such as an oxide material, for example. In various embodiments, the inner spacers **126** contain oxygen. The inner spacers **126** may also contain Si. In one embodiment, the inner spacers **126** include silicon oxycarbonitride (SiOCN). In some embodiments, the inner spacers **126** include silicon nitride (SiN), and some amount of native oxide has formed on the SiN in one embodiment (e.g., due to exposure to the ambient environment). Of course, other materials may also be selected for use as the inner spacers **126**.

[0035] The inner spacers **136** may be the same (structurally and/or materially) as the inner spacers **126**, as illustrated, or may have differences. In the initial state **108**, the inner spacers **126** are in the openings **128** while the inner spacers **136** are located between the structures **132** and the sacrificial layers **137**. The target material **135** of the sacrificial layers **137** is a different material than the first material **125**. In various embodiments, the target material **135** is a silicon-containing material, and the target material **135** is SiGe in one embodiment.

[0036] The initial state **108** is provided as an example starting point for the etching process **100**, but other process steps (e.g., that lead to the substrate **110** being in the initial state **108**) may be thought of as part of the etching process **100** in some cases. One example might be a preliminary etch step that is used to form the openings **128**. For example, prior to the initial state **108**, the shorter channel devices **120** of the substrate **110** may include sacrificial layers between the short channel layers **123** (which may be the same or different than the sacrificial layers **137**) that are etched in a channel release process for the shorter channel devices **120** that result in the initial state **108**.

[0037] Referring to FIG. **1B**, the substrate **110** is exposed to a blocking gas **142** during a selective formation step **101** of the etching process **100**. The blocking gas **142** selectively forms blocking layer **140** on the exposed surfaces of the inner spacers **126** in the openings **128**. The blocking gas **142** is selected to (i.e., configured to) interact with the material of the inner spacers **126** so that the blocking layer **140** are formed on the inner spacers **126** while the blocking gas **142** forms little or no material on undesirable surfaces (such as at least not forming a blocking layer on the target material **135**, for example).

[0038] The blocking gas **142** may be a single gas or a combination of gases. In various embodiments, the blocking gas **142** includes an ammonium precursor, and includes ammonia (NH₃) gas in one embodiment. The blocking gas **142** may also include a fluorine source, such as hydrogen fluoride (HF) gas, in one embodiment. For example, in some embodiments, an ammonium precursor and a fluorine source combine to form ammonium fluoride (AF) as the blocking layer **140**. In one embodiment, the inner spacers **126** include silicon, and the blocking layer **140** includes or is entirely ammonium fluorosilicate (AFS). The blocking gas **142** may also include additional gases (e.g., other than those directly involved in the formation of the material of the blocking gas **142**). For example, the blocking gas **142** may also include carrier gases (e.g., inert or semi-inert gases such as nitrogen (N₂), noble gases (e.g., argon (Ar), krypton (Kr), etc.), reactive gases, such as catalysts, and others.

[0039] The selective formation of the blocking gas **142** may be based on a variety of mechanisms, one of which may be sticking coefficient that varies based on material. For instance, the blocking gas **142** may form a material selected to (i.e., configured to) form quickly on the inner spacers **126** and more slowly on other materials present on the substrate **110** (e.g., sufficiently slowly so as to modulate the deposition regime based on time). In some embodiments, such as for AF and AFS blocking layer materials, the blocking layer **140** may form faster on oxygen-containing materials, such as oxides (including native oxide formed on non-oxides, such as SiN, for example). In some cases, substantially no material may form on other materials, such as the target material **135** of the sacrificial layers **137**, during the formation of the blocking layer **140**. This may allow time-based selective deposition by exposing the substrate **110** to the blocking gas **142** for a duration long enough to form the blocking layer **140**, but short enough to prevent significant blocking material from building up elsewhere.

[0040] The selective formation step **101** may include other controllable parameters, such as temperature (substrate, chamber, gas, etc.) and pressure (which may be modulated by controlling flowrates of the constituent gases of the blocking gas **142**, vacuum pumping speed, etc.). For example, the formation temperature **145** (e.g., the substrate temperature) of the selective formation step **101** may be less than about 80° C., and is in the range of about 0° C. to about 55° C. in some embodiments. Similarly, the formation pressure **146** of the selective formation step **101** may be less than about 2000 mT, and is in the range of about 10 mT to about 2000 mT in one embodiment.

[0041] Referring to now FIG. 1C, the substrate **110** is exposed to an etchant gas **152** in a etch step **102** of the etching process **100**. The etchant gas **152** is configured to etch the target material **135** of the sacrificial layers **137** to form openings **138** without etching the long channel layers **133**. During the etch step **102**, the blocking layer **140** is configured to protect the structures **122** from the etchant gas **152** (i.e., inhibit or block diffusion of the etchant gas **152** through the inner spacers **126** and into the structures **122**, such as into SiGe source/drain structures, for example). In particular, the inner spacers **126** cover second material surfaces **144** of the structures **122**, but may not prevent diffusion of the etchant gas **152** for the additional etching time needed to release the long channel layers **133** forming the openings **138**.

[0042] The etchant gas **152** may also be a single gas or a combination of gases. Some of the gases of the etchant gas **152** may be the same as the blocking gas **142**, but some gases are different. The etchant gas **152** includes at least one fluorine-containing gas in various embodiments, and includes chlorine trifluoride (ClF.sub.3) in some embodiments, and fluorine (F.sub.2) gas in some embodiments. For example, the etchant gas **152** may include both ClF.sub.3 gas and F.sub.2. In one embodiment, the etchant gas **152** includes ClF.sub.3 gas, F.sub.2 gas, and HF gas (while still possibly including other gases, such as Ar, N.sub.2, etc.).

[0043] The degree of overetch that the shorter channel devices **120** can tolerate while the etching process **100** still has the desired results (e.g., yield) may be referred to as the overetch margin of the etching process **100**. For example, overetch margin for the etching process **100** may be the amount of etching that the smallest etching target on the substrate **110** can withstand (e.g., the shorter channel devices **120**) and may need to be at least large enough to accommodate the largest etching target on the substrate **110** (e.g., the longer channel devices **130**). In the specific application of a channel release process shown here, it may be desirable to increase the overetch margin to allow for the completion of the channel release of the long channel layers **133** without damaging the shorter channel devices **120**.

[0044] In conventional etching processes, damage from overetching may begin for the shorter channel devices **120** very early (e.g., immediately after the short channel layers **123** are fully released) and quickly become untenable, such as about 10% of the sites being damaged at about 50 nm overetch and rapidly climbing to greater than 75% damaged sites at about 125 nm overetch. In contrast, damaged sites may advantageously not even appear until about 200 nm overetch (or higher), such as when an AF or AFS blocking layer is used.

[0045] Similar to the selective formation step **101**, the etch step **102** may be performed at certain temperatures and pressures. For example, the etch temperature **155** of the etch step **102** may be less than about 80° C., and is in the range of about 0° C. to about 55° C. in some embodiments. This may be similar to the ranges of the formation temperature **145**, although the specific temperature values or ranges do not have to be identical between the selective formation step **101** and the etch step **102** for a given implementation of the etching process **100**. Similarly, the etch pressure **156** of the etch step **102** may be less than about 500 mT, and is in the range of about 10 mT to about 500 mT in one embodiment. In various embodiments, the etch pressure **156** is lower than the formation pressure **146** (e.g., a relatively low pressure compared to the relatively medium pressure of the selective formation step **101**).

[0046] Now turning to FIG. 1D, the blocking layer **140** is removed during a removal step **103** of the etching process **100**. For example, the material of the blocking layer **140** may be volatile at elevated temperatures, allowing for the blocking layer **140** to be removed by applying heat to the substrate **110** during the removal step **103**. In various embodiments, a removal temperature **165** of the removal step **103** is higher than both the formation temperature **145** and the etch temperature **155**, such as greater than about 80° C. in some embodiments. In one embodiment, the removal temperature **165** is in the range of about 100° C. to about 200° C.

[0047] The removal step **103** may also be performed at a relatively high temperature compared to the previous steps. For example, a removal pressure **166** of the removal step **103** is higher than one

or both of the formation pressure **146** and the etch pressure **156** in various embodiments. In some embodiments, the removal pressure **166** is greater than about 1000 mT, and the removal pressure **166** is in the range of about 1000 mT to about 5000 mT in one embodiment.

[0048] Based on the selection of the material of the blocking layer **140**, the removal step **103** may have the advantage of being easily removable, such as by simply elevating the temperature (e.g., baking) of the substrate **110** to a temperature within the thermal budget. Moreover, the resulting surfaces (including the inner spacers **126**) may be pristine after the removal step **103**. That is, the atomic concentrations of the inner spacers **126** before formation and after removal of the blocking layer **140** may advantageously remain the same to within 1% (or even lower).

[0049] FIGS. 2A-2C illustrate another example etching process that uses a blocking layer to inhibit diffusion while etching a target material, where FIG. 2A shows an initial state of a substrate with inner spacers in openings of a vertical stack of layers, FIG. 2B shows an optional pretreatment step that modifies surfaces of the inner spacers, and FIG. 2C shows a combined step of selectively forming the blocking layer on the inner spacers while etching the target material in accordance with embodiments of the invention. The etching process of FIGS. 2A-2C may be a specific implementation of other etching processes described herein such as the etching process of FIGS. 1A-1D, for example. Similarly labeled elements may be as previously described.

[0050] Referring to FIG. 2A, an etching process **200** begins with an initial state **208** of a substrate **210** that is similar to the initial state **108** of the etching process **100** where the substrate **210** includes shorter channel devices and longer channel devices. The shorter channel devices have a first vertical stack of layers **224** (e.g., a suspended channel structure) with short channel layers **223** suspended between structures **222** (e.g., source/drain structures). The short channel layers **223** are separated by inner spacers **226** disposed in openings **228** between the short channel layers **223**. The longer channel devices may have a second vertical stack of layers **234** disposed between structures **232**. The second vertical stack of layers **234** includes long channel layers **233** separated by inner spacers **236** and sacrificial layers **237** that are formed of a target material **235**.

[0051] It should be noted that here and in the following a convention has been adopted for brevity and clarity wherein elements adhering to the pattern [x10] where 'x' is the figure number may be related implementations of a substrate in various embodiments. For example, the substrate **210** may be similar to the substrate **110** except as otherwise stated. An analogous convention has also been adopted for other elements as made clear by the use of similar terms in conjunction with the aforementioned numbering system.

[0052] Referring to FIGS. 2B and 2C, the etching process **200** differs from the etching process **100** in that the selective formation and etching steps are combined into a combined step **205** during which the substrate **210** is exposed to both a blocking gas **242** and an etchant gas **252**. Specifically, a blocking layer **240** is formed on the inner spacers **226** concurrently with the etching of the target material **235** to form openings **238**. Additionally, an optional pretreatment step **204** may also be included to pretreat surfaces of the inner spacers **226** in preparation for the formation of the blocking layer **240** using the blocking gas **242**. During the optional pretreatment step **204**, the substrate **210** may be exposed to an intermediate gas **247** that modifies the inner spacers **226** to form modified inner spacer surfaces **241**. After the combined step **205**, the sacrificial layers **237** may be gone (e.g., a full channel release of the long channel layers **233** extending the openings **238** to the inner spacers **236**) while material of the blocking layer **240** remains on the inner spacers **226**. The etching process **200** may then proceed to a removal step, which is the same as the removal step **103** of the etching process **100** of FIG. 1D.

[0053] The blocking gas **242** and the etchant gas **252** may be the same or different as the analogous gases in the selective formation step **101** and the etch step **102** of the etching process **100**. For example, the gases included in the etchant gas **252** may depend on the target material **235** which may be the same or different than the target material **135**. However, in some cases, the inclusion of the blocking gas **242** may make changes to the etchant gas **252** desirable and the etchant gas **252**

may be different despite the target material **235** being the same as the target material **135**. Similarly, the blocking gas **242** may be the same as the blocking gas **142** (such as when the optional pretreatment step **204** is not included), but may also be different. In one embodiment, the intermediate gas **247** includes NH.sub.3 gas while the blocking gas **242** includes HF gas.

[0054] The optional pretreatment step **204** and the combined step **205** may be performed at certain temperatures and pressures. These may have some similarity to the temperatures and pressures of corresponding steps in the etching process **100**. For example, an etch temperature **255** and an etch pressure **256** of the combined step **205** may be similar to that of the etch step **102** of etching process **100** (e.g., despite the inclusion of the blocking gas **242**, for example). Although not directly analogous, an intermediate temperature **243** and an intermediate pressure **244** of the optional pretreatment step **204** (when included) may be similar to the formation temperature **145** and the formation pressure **146** of the selective formation step **101** of the etching process **100**. For example, this may be thought of as similar in the sense that the bare surfaces of the inner spacers **226** may be affected by one or more similar gases as the inner spacers **126** in the selective formation step **101**, such as NH.sub.3 gas, for example.

[0055] FIG. **3** illustrates an example system that may be used to perform one or more steps of the etching processes without breaking vacuum in accordance with embodiments of the invention. The system of FIG. **3** may be used to perform some or all of any of the etching processes and methods apparent from the descriptions herein, such as the etching processes of FIGS. **1A-1D** and **2A-2C** and the method of FIG. **5**, as examples. Similarly labeled elements may be as previously described.

[0056] Referring to FIG. **3**, a system **300** (e.g., an etching system) includes a substrate support **360** disposed within a vacuum environment **371**, such as a processing chamber **370**, and configured to support a substrate **310**. A blocking source **372** (e.g., a gas source or sources that include a blocking gas), an etchant source **374** (e.g., a gas source or sources including one or more reactive gases configured to etch a target material) are fluidically coupled to the processing chamber **370** through one or more valves, such as a blocking valve **373** and an etchant valve **375**. Additional gas sources and valves may also be included in the system **300**. For example, an optional additional gas source **376** (e.g., a gas source or sources including additional gases, which may be any type of gas, such as carrier gases, additional reactants and precursors, stabilizers, catalysts and others) may be fluidically coupled to the processing chamber **370** through an optional additional gas valve **377**. An exhaust valve **389** is also included to evacuate the processing chamber **370** during the processes performed therein, such as the etching processes as described in the foregoing, preceding or subsequent etching processes, and others.

[0057] The processing chamber **370** may be any suitable etch chamber and may also be usable as a deposition chamber. In various embodiments, process steps of an etching process performed by the system **300** (e.g., a selective formation step, an etching step, a removal step, etc.) may be performed without generating plasma. In other cases, plasma may be generated during some or all of the process steps. The processing chamber **370** may be used for some or all of the process steps of an etching process. In various embodiments, a selective formation step of a blocking layer and an etching step of a target material are performed in situ in the processing chamber **370** (i.e., in place in the same chamber). In one embodiment, the selective formation step, the etching step, and a removal step of the blocking layer are all performed in situ in the processing chamber **370**. In another embodiment, the removal step is performed in a different chamber than the selective formation step and the etching step.

[0058] An optional temperature monitor **386** may also be included to monitor and/or aid in controlling the temperature of the substrate **310** and the environment in the processing chamber **370**. A temperature control device **387** (heater, cooler, or combination thereof) may be included to elevate or reduce the temperature of the substrate **310** above/below the equilibrium temperature at the substrate **310** during the process steps (although some process steps may be performed at ambient temperatures). An optional motor **388** may also be included to improve etch/deposition

uniformity.

[0059] A controller **380** is operatively coupled to the one or more valves (the blocking valve **373**, the etchant valve **375**, the optional additional gas valve **377**, etc.), and may be operatively coupled to any of the optional temperature monitor **386**, the temperature control device **387**, the optional motor **388**, and the exhaust valve **389**. The controller **380** includes a processor **382** and a memory **384** (i.e., a non-transitory computer-readable medium) that stores a program including instructions that, when executed by the processor **382**, perform processes such as the etching processes described herein. For example, the memory **384** may have volatile memory (e.g., random access memory (RAM)) and non-volatile memory (e.g., flash memory). Alternatively, the program may be stored in physical memory at a remote location, such as in cloud storage. The processor **382** may be any suitable processor, such as the processor of a microcontroller, a general-purpose processor (such as a central processing unit (CPU), a microprocessor, a field-programmable gate array (FPGA), an application-specific integrated circuit (ASIC), and others.

[0060] FIG. **4** illustrates another example system that may be used to perform one or more steps of the etching processes without breaking vacuum in accordance with embodiments of the invention. The system of FIG. **4** may be used to perform some or all of any of the etching processes and methods apparent from the descriptions herein, such as the etching processes of FIGS. **1A-1D** and **2A-2C** and the method of FIG. **5**, as examples. Similarly labeled elements may be as previously described.

[0061] Referring to FIG. **4**, a system **400** is similar to the system **300** except that the system **400** includes two processing chambers (a processing chamber **470** and at least one additional processing chamber **478**) in a vacuum environment **471**. That is, the system **400** may be a platform that includes several tools and is configured to perform processes in two or more regions (e.g., chambers) without breaking vacuum (e.g., in the vacuum environment **471**). Of course, the pressure in the various regions of the system **400** may be individually controlled relative to one another, but the system **400** is a closed system that maintains the vacuum environment **471** below external pressures and prevents gases from the external environment from entering the vacuum environment **471**. The processing chamber **470** may be similar to the processing chamber **370** (i.e., various additional features and components may be included for the processing chamber **470** as the processing chamber **370**, but many of these features are not illustrated in FIG. **4** for the sake of simplicity).

[0062] The system **400** includes a substrate support **460** disposed within the vacuum environment **471** and configured to support a substrate **410**. For example, the substrate support **460** may be configured to be moved between the processing chamber **470** and the vacuum environment **471**. Alternatively, the substrate **410** may be transferred between substrate supports when being moved between the processing chamber **470** and the vacuum environment **471**. A blocking source **472**, an etchant source **474**, and an optional additional gas source **476** are fluidically coupled to the processing chamber **470** through one or more valves, such as a blocking valve **473** an etchant valve **475**, and an optional additional gas valve **477**.

[0063] The processing chamber **470** may be any suitable etch chamber and may also be usable as a deposition chamber. The processing chamber **470** may be used for some of the process steps of an etching process while the additional processing chamber **478** may be used for other process steps of the etching process. The additional processing chamber **478** may be any suitable chamber (e.g., for removal of a blocking layer, for example), such as a baking chamber. In various embodiments, all of the process steps of an etching process are performed in the system **400** without breaking vacuum (i.e., in the vacuum environment **471**). In one embodiment, a selective formation step of a blocking layer and an etching step of a target material are performed in situ in the processing chamber **470** (i.e., in place in the same chamber) while a removal step of the blocking layer is performed in the additional processing chamber **478**.

[0064] A controller **480** (e.g., optionally as part of a control system **481**, which may include one or

more additional controllers, such as controller **483**, that are specialized to control various aspects of the system **400**) is operatively coupled to the one or more valves (the blocking valve **473**, the etchant valve **475**, the optional additional gas valve **477**, etc.), and may be operatively coupled to the substrate support **460** (or various substrate transport mechanisms), as well as any optional components (not shown) like an optional temperature monitor, optional temperature control device, optional motor, exhaust valve. The controller **480** includes a processor **482** and a memory **484** (i.e., a non-transitory computer-readable medium) that stores a program including instructions that, when executed by the processor **482**, perform processes such as the etching processes described herein.

[0065] FIG. 5 illustrates an example method etching a target material of a substrate that also includes a vertical stack of layers of a first material suspended between structures of a second material in accordance with embodiments of the invention. The method of FIG. 5 may be combined with other methods and performed using the systems and apparatuses as described herein. For example, the method of FIG. 5 may be combined with any of the embodiments of FIGS. 1A-4. Although shown in a logical order, the arrangement and numbering of the steps of FIG. 5 are not intended to be limited. The method steps of FIG. 5 may be performed in any suitable order or concurrently with one another as may be apparent to a person of skill in the art.

[0066] Referring to FIG. 5, a method **500** of etching a target material may start at an initial state **508** with a substrate including the target material that also includes a vertical stack of layers of a first material (e.g., channel layers, such as Si channel layers) suspended between structures of a second material (e.g., source/drain structures, such as SiGe source/drain structures). Although there is no strict structural requirement for the method **500**, the vertical stack of layers is an example category of applications to which the method **500** may be well-suited. The vertical stack of layers may be an intermediate or final structure that is part of a three-dimensional device, such as a three-dimensional channel structure including suspended channel layers of a GAA transistor (e.g., GAA FET).

[0067] Inner spacers (e.g., comprising oxygen, such as an oxide), may be located in openings between the layers of the first material arranged so that they cover surfaces of the second material, such as directly contacting the surfaces of the second material structures in the openings, but direct contact is not required. In some cases, additional structures may be included between the inner spacers and the second material or the inner spacers may be set apart from the second material within the openings.

[0068] The length of the layers in the vertical stack (e.g., the channel length between source/drain structures) may be chosen to be any desired value, but is shorter than the length of the structures that include the target material in some embodiments. For example, in the specific example where the vertical stack of layers is a channel structure included in shorter channel devices, the target material may be sacrificial layers between channel layers of a longer channel device. In various embodiments, the channel length of the longer channel devices is greater than about 50 nm, and may be greater than at least about 100 nm in some embodiments. Of course, as discussed in the foregoing, embodiment etching processes (i.e., performed by the method **500**) undesirable structural damage may be entirely avoided for at least about 200 nm of overetch (or even more). and therefore, in some cases, the longer channel devices may also have channel lengths of at least about 200 nm while still achieving the desired results.

[0069] In a selective formation step **501**, a blocking layer is selectively formed on the inner spacers using a blocking gas (e.g., using a controller operatively coupled to one or more valves and executing a program that causes the one or more valves to fluidically couple the blocking gas with a processing chamber that contains the substrate). The inner spacers may include an oxygen-containing material such as an oxide or a dielectric material with a native oxide formed thereon. In one embodiment, the inner spacers include SiOCN (silicon oxycarbonitride). In other embodiments, the inner spacers include SiN (silicon nitride), such as with native oxide formed on

the surface.

[0070] The blocking gas includes one or more gases that selective deposit on the material of the inner spacers. For example, the blocking gas may form a blocking layer on oxygen-containing materials, oxides, nitrides, etc. at a sufficiently shorter timescales than the blocking layer forms on the target material so that providing the blocking gas for a short enough duration results in the blocking layer selectively forming on the inner spacers. In various embodiments, the blocking gas includes ammonia (such as ammonia gas or a gaseous compound that includes an ammonia precursor). In some embodiments, the blocking gas includes at least one fluorine-containing gas and includes HF (hydrogen fluoride) in one embodiment.

[0071] While the blocking layer may be any material that will selectively deposit on the material of the inner spacer and can be removed without affecting the inner spacer material, the blocking layer may be a compound including ammonium and fluorine. In one embodiment, the blocking layer is AF (ammonium fluoride). In another embodiment, the blocking layer is AFS (ammonium fluorosilicate).

[0072] In some embodiments, rather than beginning with a substrate in the initial state **508**, the method **500** may include an optional preliminary etch step **506** during which sacrificial layers of the vertical stack of layers (e.g., of shorter channel devices) are etched to expose the inner spacers in the openings between the layers of the first material (e.g., between the channel layers as part of a channel release process of the shorter channel devices). The optional preliminary etch step **506** may or may not be performed concurrently with the first part of a channel release process of longer channel devices. For example, in one embodiment, the optional preliminary etch step **506** is also a preliminary etch step of sacrificial layers of between channel layers of longer channel devices (that does not reach an endpoint because the channel length is longer). Since the sacrificial layers of the longer channel devices are not fully removed, inner spacers that may be included in the longer channel devices are not exposed and therefore no blocking layer would form on the longer channel devices.

[0073] In an etch step **502**, the target material is etched using an etchant gas while the blocking layer inhibits diffusion of the etchant gas into the second material (e.g., using the controller, or another controller, to cause the one or more valves to fluidically couple the etchant gas with the processing chamber). For instance, the target material may be sacrificial layers, such as SiGe layers, of a vertical stack of layers of a longer channel device that is etched using a fluorine-containing gas, such as ClF₃, F₂, or a combination thereof. The blocking layer inhibits diffusion of the etchant gas through the inner spacers and into the second material. That is, diffusion is at least slowed down and may be prohibited entirely (at least on timescales of similar order of magnitude as the etch step **502**).

[0074] The etch step **502** may be performed after the selective formation step **501**, as shown. Alternatively, etching the target material may be performed concurrently (i.e., simultaneously) with selectively forming the blocking layer, as shown in combined step **505**. In some implementations, the blocking gas or a component of the blocking gas may be included in the etch step **502** so that the blocking layer continues to be formed while etching the target material even when the selective formation step **501** is included as a separate selective formation step (shown as the arrow **511**). Further, the selective formation step **501** and the etch step **502** may be repeated as a cycle **509** (e.g., in order to maintain protection of the second material structures during further etching of the target material if the blocking layer is consumed or otherwise modified during the etch step **502**).

[0075] The blocking gas for the combined step **505** may be the same or different than the blocking gas for the selective formation step **501**. As an example of when the blocking gas may be different, an optional pretreatment step **504** may be included during which the inner spacers (e.g., an oxygen-containing material such as an oxide, or another dielectric material such as a nitride) are exposed to an intermediate gas and then further precursors of the blocking layer are included in the blocking gas of the combined step **505**. In analogy with the previous specific examples of a blocking gas, the

intermediate gas may include ammonia gas while the blocking gas provided during the combined step **505** may include HF gas (with or without ammonia gas).

[0076] After the etch step **502** (or the combined step **505**, or a cycle **509**) has reached the desired endpoint for etching the target material, the blocking layer is removed from the inner spacers in a removal step **503**. During the removal step **503**, the blocking layer is removed without affecting the material composition of the inner spacers. For example, when the inner spacers include an oxygen-containing material at exposed surfaces of the inner spacers, the blocking layer is removed from the oxygen-containing material and the oxygen-containing material has the same composition (i.e., atomic concentrations) before the selective formation step **501** as after the removal step **503** (e.g., to some tolerance such as within one percent of the atomic concentrations before the selective formation step **501**, or even lower).

[0077] In various embodiments, the material of the blocking layer is selected so that it may be fully removable (i.e., configured to be fully removable). The bonding of the blocking layer to the inner spacers may be fully reversible, such as by providing a certain threshold of energy (i.e., activation energy, which may be provided in the form of thermal energy, for example) to break the bonds and remove the blocking layer. The material of the blocking layer may be volatilized at temperatures in the above a certain range, resulting in decomposition of the material. For example, the removal step **503** may include exposing the vertical stack to a temperature of at least 80° C. (such as using a temperature control device in the substrate holder). In the specific example of AF, the AF blocking layer may then sublime as its precursor gases, which would be ammonia gas and HF gas in this case.

[0078] In various embodiments, temperature may also be controlled (substrate temperature, processing gas temperature, etc.) during one or both of the selective formation step **501** and the etch step **502** (and the optional pretreatment step **504** and the combined step **505** when included). For example, if elevated temperature results in the removal of the blocking layer, then it may be desirable to ensure that the substrate temperature is maintained below the threshold (e.g., 80° C.) before the removal step **503**, such as using one or more substrate temperature control devices operatively coupled to the controller, or an additional controller. In some embodiments, the gap between the temperature during the removal step **503** and the temperature during other steps may be larger. In one specific example, the substrate is maintained at temperatures below about 55° C. during both the selective formation step **501** and the etch step **502** while the substrate is maintained at temperatures above about 100° C. during the removal step **503**.

[0079] The selective formation step **501** and the etch step **502** (and the optional pretreatment step **504** and the combined step **505** when included) may be performed in the same processing chamber (e.g., an etching chamber). The removal step **503** may also be performed in the same processing chamber. However, in some embodiments it may be desirable to perform the removal step **503** in a different (i.e., additional) processing chamber, such as to maintain cleanliness in the etching chamber. In this case, the method **500** may also include a loading step **507** where the substrate is moved to (i.e., loaded into) the additional processing chamber between the etch step **502** (or the combined step **505**) and the removal step **503**. Notably, this may still be performed in the same vacuum environment of a system that is being used to perform the method **500** (such as the system **400** of FIG. 4, for example). That is, the method **500** may be performed without breaking vacuum all in the same processing chamber or in multiple processing chambers of the same platform.

[0080] Example embodiments of the invention are summarized here. Other embodiments can also be understood from the entirety of the specification as well as the claims filed herein.

[0081] Example 1. A method of etching a target material of a substrate that also includes a vertical stack of layers of a first material suspended between structures of a second material, the method including: selectively forming a blocking layer on an oxygen-containing material using ammonia gas and at least one fluorine-containing gas, the oxygen-containing material covering surfaces of the second material in openings between the layers of the first material; etching the target material

using an etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the second material; and removing the blocking layer from the oxygen-containing material by exposing the vertical stack to a temperature of at least 80° C.

[0082] Example 2. The method of example 1, where selectively forming the blocking layer and etching the target material are both performed in the same processing chamber.

[0083] Example 3. The method of one of examples 1 and 2, where etching the target material is performed after selectively forming the blocking layer.

[0084] Example 4. The method of one of examples 1 and 2, where selectively forming the blocking layer is performed concurrently with etching the target material.

[0085] Example 5. The method of example 4, where selectively forming the blocking layer includes exposing the oxygen-containing material to the ammonia gas before etching the target material, and then exposing the oxygen-containing material to the at least one fluorine gas concurrently with etching the target material.

[0086] Example 6. The method of one of examples 1 to 5, where the blocking layer includes ammonium fluorosilicate or ammonium fluoride.

[0087] Example 7. The method of one of examples 1 to 6, where the at least one fluorine-containing gas includes hydrogen fluoride (HF).

[0088] Example 8. The method of one of examples 1 to 7, where selectively forming the blocking layer and etching the target material are performed at temperatures less than 80° C.

[0089] Example 9. The method of one of examples 1 to 8, where selectively forming the blocking layer, etching the target material, and removing the blocking layer are performed without breaking vacuum.

[0090] Example 10. The method of one of examples 1 to 9, where atomic concentrations of the oxygen-containing material before selectively forming the blocking layer are within one percent of atomic concentrations of the oxygen-containing material after removing the blocking layer.

[0091] Example 11. The method of one of examples 1 to 10, further including repeating selectively forming the blocking layer and etching the target material as a cycle before removing the blocking layer.

[0092] Example 12. A channel release method for longer channel devices of a substrate that also includes shorter channel devices, the method including performing the following steps without breaking vacuum: selectively forming a blocking layer on inner spacers of the shorter channel devices, the inner spacers covering surfaces of silicon germanium (SiGe) source/drain structures in openings between silicon (Si) layers suspended between the SiGe source/drain structures; etching SiGe layers of the longer channel devices using an etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the SiGe source/drain structures; and removing the blocking layer from the inner spacers by exposing the shorter channel devices to a temperature of at least 80° C.

[0093] Example 13. The channel release method of example 12, where selectively forming the blocking layer on the inner spacers of the shorter channel devices and etching the SiGe layers of the longer channel devices are performed in the same processing chamber.

[0094] Example 14. The channel release method of one of examples 12 and 13, further including: etching SiGe layers of the shorter channel devices to expose the inner spacers in the openings using the etchant gas before selectively forming the blocking layer.

[0095] Example 15. The channel release method of one of examples 12 to 14, where the blocking layer includes ammonium fluorosilicate or ammonium fluoride, and where the inner spacers include silicon oxycarbonitride (SiOCN).

[0096] Example 16. The channel release method of one of examples 12 to 14, where the blocking layer includes ammonium fluorosilicate or ammonium fluoride, and where the inner spacers include silicon nitride (SiN) and native oxide.

[0097] Example 17. The channel release method of one of examples 12 to 16, where the longer channel devices include a channel length of at least about 50 nm.

[0098] Example 18. A system including: a processing chamber; a substrate support configured to support a substrate within the processing chamber, the substrate including a target material and a vertical stack of layers of a first material suspended between structures of a second material; one or more valves configured to fluidically couple a blocking gas and an etchant gas to the processing chamber; and a controller operatively coupled to the one or more valves, the controller including a processor and a non-transitory computer-readable medium storing a program including instructions that, when executed by the processor, perform a method without breaking a vacuum environment of the system, the method including: selectively forming, in the processing chamber, a blocking layer on an inner spacer material covering surfaces of the second material in openings between the layers of the first material using the blocking gas; etching, in the processing chamber, the target material using the etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the second material; and removing the blocking layer from the inner spacer material.

[0099] Example 19. The system of example 18, further including: an additional processing chamber fluidically coupled to the vacuum environment of the system, the method further including moving the substrate to the additional processing chamber, where removing the blocking layer is performed in the additional processing chamber.

[0100] Example 20. The system of one of examples 18 and 19, further including: one or more substrate temperature control devices operatively coupled to the controller, where selectively forming the blocking layer and etching the target material include maintaining the substrate at temperatures below about 55° C. using the one or more substrate temperature control devices, and where removing the blocking layer includes maintaining the substrate at temperatures above about 100° C. using the one or more substrate temperature control devices.

[0101] While this invention has been described with reference to illustrative embodiments, this description is not intended to be construed in a limiting sense. Various modifications and combinations of the illustrative embodiments, as well as other embodiments of the invention, will be apparent to persons skilled in the art upon reference to the description. It is therefore intended that the appended claims encompass any such modifications or embodiments.

Claims

1. A method of etching a target material of a substrate that also comprises a vertical stack of layers of a first material suspended between structures of a second material, the method comprising: selectively forming a blocking layer on an oxygen-containing material using ammonia gas and at least one fluorine-containing gas, the oxygen-containing material covering surfaces of the second material in openings between the layers of the first material; etching the target material using an etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the second material; and removing the blocking layer from the oxygen-containing material by exposing the vertical stack to an elevated temperature relative to that of selectively forming the blocking layer.
2. The method of claim 1, wherein selectively forming the blocking layer and etching the target material are both performed in the same processing chamber.
3. The method of claim 1, wherein etching the target material is performed after selectively forming the blocking layer.
4. The method of claim 1, wherein selectively forming the blocking layer is performed concurrently with etching the target material.
5. The method of claim 4, wherein selectively forming the blocking layer comprises exposing the oxygen-containing material to the ammonia gas before etching the target material, and then exposing the oxygen-containing material to the at least one fluorine gas concurrently with etching the target material.
6. The method of claim 1, wherein the blocking layer comprises ammonium fluorosilicate or ammonium fluoride.

7. The method of claim 1, wherein the at least one fluorine-containing gas comprises hydrogen fluoride (HF).
8. The method of claim 1, wherein selectively forming the blocking layer and etching the target material are performed at temperatures less than 80° C.
9. The method of claim 1, wherein selectively forming the blocking layer, etching the target material, and removing the blocking layer are performed without breaking vacuum.
10. The method of claim 1, wherein atomic concentrations of the oxygen-containing material before selectively forming the blocking layer are within one percent of atomic concentrations of the oxygen-containing material after removing the blocking layer.
11. The method of claim 1, further comprising repeating selectively forming the blocking layer and etching the target material as a cycle before removing the blocking layer.
12. A channel release method for longer channel devices of a substrate that also comprises shorter channel devices, the method comprising performing the following steps without breaking vacuum: selectively forming a blocking layer on inner spacers of the shorter channel devices, the inner spacers covering surfaces of silicon germanium (SiGe) source/drain structures in openings between silicon (Si) layers suspended between the SiGe source/drain structures; etching SiGe layers of the longer channel devices using an etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the SiGe source/drain structures; and removing the blocking layer from the inner spacers by exposing the shorter channel devices to an elevated temperature relative to that of selectively forming the blocking layer.
13. The channel release method of claim 12, wherein selectively forming the blocking layer on the inner spacers of the shorter channel devices and etching the SiGe layers of the longer channel devices are performed in the same processing chamber.
14. The channel release method of claim 12, further comprising: etching SiGe layers of the shorter channel devices to expose the inner spacers in the openings using the etchant gas before selectively forming the blocking layer.
15. The channel release method of claim 12, wherein the blocking layer comprises ammonium fluorosilicate or ammonium fluoride, and wherein the inner spacers comprise silicon oxycarbonitride (SiOCN).
16. The channel release method of claim 12, wherein the blocking layer comprises ammonium fluorosilicate or ammonium fluoride, and wherein the inner spacers comprise silicon nitride (SiN) and native oxide.
17. The channel release method of claim 12, wherein the longer channel devices comprise a channel length of at least about 50 nm.
18. A system comprising: a processing chamber; a substrate support configured to support a substrate within the processing chamber, the substrate comprising a target material and a vertical stack of layers of a first material suspended between structures of a second material; one or more valves configured to fluidically couple a blocking gas and an etchant gas to the processing chamber; and a controller operatively coupled to the one or more valves, the controller comprising a processor and a non-transitory computer-readable medium storing a program including instructions that, when executed by the processor, perform a method without breaking a vacuum environment of the system, the method comprising: selectively forming, in the processing chamber, a blocking layer on an inner spacer material covering surfaces of the second material in openings between the layers of the first material using the blocking gas; etching, in the processing chamber, the target material using the etchant gas, the blocking layer inhibiting diffusion of the etchant gas into the second material; and removing the blocking layer from the inner spacer material.
19. The system of claim 18, further comprising: an additional processing chamber fluidically coupled to the vacuum environment of the system, the method further comprising moving the substrate to the additional processing chamber, wherein removing the blocking layer is performed in the additional processing chamber.

20. The system of claim 18, further comprising: one or more substrate temperature control devices operatively coupled to the controller, wherein selectively forming the blocking layer and etching the target material comprise maintaining the substrate at temperatures below about 55° C. using the one or more substrate temperature control devices, and wherein removing the blocking layer comprises maintaining the substrate at temperatures above about 100° C. using the one or more substrate temperature control devices.
