

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279480

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

Su; Chi Cheung et al.

IONIC LIQUID ELECTROLYTES FOR LITHIUM BATTERIES

Abstract

An electrochemical cell includes a cathode of oxygen or a metal oxide; an anode comprising lithium metal; and an electrolyte including a lithium sulfonylimide salt, a terminally fluorinated glycol ether, and an ionic liquid.

Inventors: Su; Chi Cheung (Westmont, IL), Amine; Khalil (Oakbrook, IL)

Applicant: UCHICAGO ARGONNE, LLC (Chicago, IL)

Family ID: 96880543

Assignee: UCHICAGO ARGONNE, LLC (Chicago, IL)

Appl. No.: 18/595327

Filed: March 04, 2024

Publication Classification

Int. Cl.: H01M10/0569 (20100101); H01M10/0525 (20100101); H01M10/0568 (20100101); H01M50/417 (20210101); H01M50/446 (20210101)

U.S. Cl.:

CPC H01M10/0569 (20130101); H01M10/0568 (20130101); H01M50/417 (20210101); H01M50/446 (20210101); H01M10/0525 (20130101); H01M2300/0034 (20130101)

Background/Summary

FIELD

[0002] The present technology is generally related to lithium rechargeable batteries. More particularly the technology relates to the use of short-chain terminally fluorinated glycol ethers and

lithium fluorosulfonylimide salt in an electrochemical cell having a metallic lithium anode.

SUMMARY

[0003] In one aspect, an electrochemical cell is provided having a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; a separator; and an electrolyte comprising a lithium fluorosulfonylimide salt, a terminally fluorinated glycol ether, and optionally an electrolyte additive, an aprotic gel polymer, ionic liquids, or a mixture of any two or more thereof. In some embodiments, the electrochemical cell is a lithium battery.

[0004] In another aspect, an electrochemical cell includes: a cathode comprising oxygen or a metal oxide, an anode comprising lithium metal, a separator, and an electrolyte. The electrolyte includes a lithium fluorinated sulfonylimide salt, a terminally fluorinated glycol ether of Formula (I) ($R_{sup.1}(O(CH_{sub.2})_{sub.m})_{sub.x}(O(CH_{sub.2})_{sub.n})_{sub.y}OR_{sup.2}$ (I)), and an ionic liquid, wherein: $R_{sup.1}$ is a fluorinated alkyl, $R_{sup.2}$ is a fluorinated alkyl, m is 1, 2, or 3, n is 1, 2, or 3, and x and y are each independently 0, 1, or 2, with the provisos that both x and y are not 0 and $x+y \leq 3$. In some embodiments, $R_{sup.1}$ is —

$(CH_{sub.2})_{sub.q}(CR_{sup.4}R_{sup.5})_{sub.p}C(R_{sup.3})_{sub.3}$; $R_{sup.2}$ is —

$(CH_{sub.2})_{sub.v}(CR_{sup.4'}R_{sup.5'})_{sub.w}C(R_{sup.3})_{sub.3}$; $R_{sup.3}$, $R_{sup.4}$, and $R_{sup.5}$ are each independently H or F, with the proviso that at least one of $R_{sup.3}$, $R_{sup.4}$, and $R_{sup.5}$ is F; $R_{sup.3}$, $R_{sup.4'}$, and $R_{sup.5'}$ are each independently H or F, with the proviso that at least one of $R_{sup.3'}$, $R_{sup.4'}$, and $R_{sup.5'}$ is F; q is 0, 1, 2, or 3; p is 0, 1, 2, 3, 4, 5, or 6; v is 0, 1, or 2; and w is 0, 1, 2, 3, 4, 5, or 6. In other embodiments, the terminally fluorinated glycol ether is 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethane, or a mixture thereof.

[0005] In some embodiments, the ionic liquid may be a compound represented by one of Formula (I), Formula (II), or a mixture of any two or more thereof:

##STR00001##

In the above formulae, $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually H, alkyl, or $OR_{sup.24}$; $R_{sup.13}$ to $R_{sup.23}$ are individually H, F, Cl, Br, I, $OR_{sup.24}$, alkyl, alkenyl, alkynyl, aryl, aralkyl, heterocyclyl, heterocyclylalkyl, cycloalkyl, cycloalkylalkyl, $-C(O)R_{sup.24}$, $-C(O)OR_{sup.24}$, or $-OC(O)R_{sup.25}$ where each $R_{sup.24}$ is individually H or alkyl; each $R_{sup.25}$ is individually H or alkyl; and each A individually is a counterion (counter anion). In some embodiments, the ionic liquid may include a compound represented by Formula (I). In other embodiments, the ionic liquid may include a compound represented by Formula (II).

[0006] In some embodiments, $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually H, $C_{sub.1}$ to $C_{sub.6}$ alkyl, or $OR_{sup.24}$ where $R_{sup.24}$ is $C_{sub.1}$ to $C_{sub.6}$ alkyl; and $R_{sup.13}$ to $R_{sup.23}$ are individually H or $C_{sub.1}$ to $C_{sub.6}$ alkyl. In some embodiments, $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually H; and $R_{sup.13}$ to $R_{sup.23}$ are individually H, methyl, ethyl, propyl, or butyl. In other embodiments, $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually H, methyl, ethyl, propyl, butyl, methoxy, ethoxy, n-propoxy, iso-propoxy, n-butyl, sec-butyl, iso-butyl, or tert-butyl; and $R_{sup.13}$ to $R_{sup.23}$ are individually H, methyl, ethyl, propyl, or butyl. In any such embodiments, the ionic liquid may be a salt of N-methyl-N-propylpyrrolidinium, N-methyl-N-butylpyrrolidinium, 1-ethyl-3-methylimidazolium, or 1-methoxyethyl-3-methylpyrrolidinium. In any such embodiments, the salt may be a bis(fluorosulfonyl)imide salt. For example, in some such embodiments, the ionic liquid include N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide, N-methyl-N-butylpyrrolidinium bis(fluorosulfonyl)imide, 1-ethyl-3-methylimidazolium bis(fluorosulfonyl)imide, 1-methoxyethyl-3-methylpyrrolidinium bis(fluorosulfonyl)imide, or a mixture of any two or more thereof.

[0007] In any of the above embodiments, the separator may be a polyolefin. For example, the polyolefin may be an aluminum oxide-filled polyolefin, or, more specifically, an aluminum oxide-filled polypropylene.

[0008] In some embodiments, the terminally fluorinated glycol ether may be 1,1,2,2-

tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and the ionic liquid comprises a salt of N-methyl-N-propylpyrrolidinium. In other embodiments, the terminally fluorinated glycol ether is 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and the ionic liquid comprises N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide.

[0009] In another aspect, an electrochemical cell includes a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; a separator comprising an aluminum oxide-filled polypropylene; and an electrolyte that includes LiN(SO₂F)₂; 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a graph of cycling performance of Li||Li symmetric cells using different LiPF₆ based electrolytes, according to Example 2.

[0011] FIG. 2 is a graph of cycling performance of Li||Li symmetric cells using different lithium bis(fluoromethanesulfonyl)imide ("LiFSI") and LiPF₆ based electrolytes, according to Example 4.

[0012] FIG. 3 is a graph of cycling performance of Li||Li symmetric cells using electrolytes with LiFSI or lithium bis(trifluoromethanesulfonyl)imide ("LiTFSI dissolved in FDG, according to Example 5.

[0013] FIGS. 4A and 4B. FIG. 4A is a graph of capacity retention. FIG. 4B illustrates the corresponding Coulombic efficiency of Li||LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂ (NMC811) cell using different electrolytes cycling at 2.5V to 4.3V, according to Example 6.

[0014] FIGS. 5A and 5B. FIG. 5A is a graph of capacity retention. FIG. 5B illustrates the corresponding Coulombic efficiency of Li||LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂ (NMC811) cell using different electrolytes cycling at 3.0V to 4.4V, according to Example 7.

[0015] FIG. 6 is a graph of cycling performance of Li||Li symmetric cells using baseline LiPF₆ based electrolyte and ionic liquid electrolytes, according to Example 8.

[0016] FIG. 7 is a discharge capacity vs. cycle number graph for a Li||LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂ cell in a 2032 coin cell using 2M LiFSI in Py13 FSI electrolyte with glass fiber separator and Al₂O₃ filled separator, according to Example 9 with the cells being cycled from 3.0 V to 4.3 V at the rate of C/2.

[0017] FIG. 8A is a discharge capacity vs. cycle number graph and FIG. 8B is a Coulombic efficiency vs. cycle number graph for a Li||LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂ cell in a 2032 coin cell using 2M LiFSI in Py13 FSI; 2M LiFSI in Py13 FSI:TTE 1:4; and 2M LiFSI in Py13 FSI:FDG 1:4 (volume ratio), where the cells were cycled from 3.0 V to 4.3 V at the rate of C/2, according to Example 10.

[0018] FIG. 9 is a voltage profile graph (1st cycle) based on cells prepared with an electrolyte of 2M LiFSI in Py13 FSI; 2M LiFSI in Py13 FSI:TTE 1:4; and 2M LiFSI in Py13 FSI:FDG 1:4 (volume ratio) electrolytes, according to Example 9.

[0019] FIG. 10 is a voltage profile graph (50th cycle) based on cells prepared with an electrolyte of 2M LiFSI in Py13 FSI; 2M LiFSI in Py13 FSI:TTE 1:4; and, 2M LiFSI in Py13 FSI:FDG 1:4 (volume ratio) electrolytes, according to Example 10.

DETAILED DESCRIPTION

[0020] Various embodiments are described hereinafter. It should be noted that the specific embodiments are not intended as an exhaustive description or as a limitation to the broader aspects

discussed herein. One aspect described in conjunction with a particular embodiment is not necessarily limited to that embodiment and can be practiced with any other embodiment(s).

[0021] As used herein, “about” will be understood by persons of ordinary skill in the art and will vary to some extent depending upon the context in which it is used. If there are uses of the term which are not clear to persons of ordinary skill in the art, given the context in which it is used, “about” will mean up to plus or minus 10% of the particular term.

[0022] The use of the terms “a” and “an” and “the” and similar referents in the context of describing the elements (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. Recitation of ranges of values herein are merely intended to serve as a shorthand method of referring individually to each separate value falling within the range, unless otherwise indicated herein, and each separate value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., “such as”) provided herein, is intended merely to better illuminate the embodiments and does not pose a limitation on the scope of the claims unless otherwise stated. No language in the specification should be construed as indicating any non-claimed element as essential.

[0023] In general, “substituted” refers to an alkyl, alkenyl, alkynyl, aryl, or ether group, as defined below (e.g., an alkyl group) in which one or more bonds to a hydrogen atom contained therein are replaced by a bond to non-hydrogen or non-carbon atoms. It should be noted that unless otherwise indicated any alkyl, alkenyl, alkynyl, aryl, ether, ester, or the like may be substituted, whether indicated as substituted or not. Substituted groups also include groups in which one or more bonds to a carbon(s) or hydrogen(s) atom are replaced by one or more bonds, including double or triple bonds, to a heteroatom. Thus, a substituted group will be substituted with one or more substituents, unless otherwise specified. In some embodiments, a substituted group is substituted with 1, 2, 3, 4, 5, or 6 substituents. Examples of substituent groups include: halogens (i.e., F, Cl, Br, and I); hydroxyls; alkoxy, alkenoxy, alkynoxy, aryloxy, aralkyloxy, heterocyclyloxy, and heterocyclylalkoxy groups; carbonyls (oxo); carboxyls; esters; urethanes; oximes; hydroxylamines; alkoxyamines; aralkoxyamines; thiols; sulfides; sulfoxides; sulfones; sulfonyls; sulfonamides; amines; N-oxides; hydrazines; hydrazides; hydrazones; azides; amides; ureas; amidines; guanidines; enamines; imides; isocyanates; isothiocyanates; cyanates; thiocyanates; imines; nitro groups; nitriles (i.e., CN); and the like.

[0024] As used herein, “alkyl” groups include straight chain and branched alkyl groups having from 1 to about 20 carbon atoms, and typically from 1 to 12 carbons or, in some embodiments, from 1 to 8 carbon atoms. As employed herein, “alkyl groups” include cycloalkyl groups as defined below. Alkyl groups may be substituted or unsubstituted. Examples of straight chain alkyl groups include methyl, ethyl, n-propyl, n-butyl, n-pentyl, n-hexyl, n-heptyl, and n-octyl groups. Examples of branched alkyl groups include, but are not limited to, isopropyl, sec-butyl, t-butyl, neopentyl, and isopentyl groups. Representative substituted alkyl groups may be substituted one or more times with, for example, amino, thio, hydroxy, cyano, alkoxy, and/or halo groups such as F, Cl, Br, and I groups. As used herein the term haloalkyl is an alkyl group having one or more halo groups. In some embodiments, haloalkyl refers to a per-haloalkyl group.

[0025] Cycloalkyl groups are cyclic alkyl groups such as, but not limited to, cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, and cyclooctyl groups. In some embodiments, the cycloalkyl group has 3 to 8 ring members, whereas in other embodiments the number of ring carbon atoms range from 3 to 5, 6, or 7. Cycloalkyl groups may be substituted or unsubstituted. Cycloalkyl groups further include polycyclic cycloalkyl groups such as, but not limited to, norbornyl, adamantyl, bornyl, camphenyl, isocamphenyl, and carenyl groups, and fused rings such as, but not limited to, decalynyl, and the like. Cycloalkyl groups also include rings that are

substituted with straight or branched chain alkyl groups as defined above. Representative substituted cycloalkyl groups may be mono-substituted or substituted more than once, such as, but not limited to: 2,2-; 2,3-; 2,4-; 2,5-; or 2,6-disubstituted cyclohexyl groups or mono-, di-, or tri-substituted norbornyl or cycloheptyl groups, which may be substituted with, for example, alkyl, alkoxy, amino, thio, hydroxy, cyano, and/or halo groups.

[0026] Alkenyl groups are straight chain, branched or cyclic alkyl groups having 2 to about 20 carbon atoms, and further including at least one double bond. In some embodiments alkenyl groups have from 1 to 12 carbons, or, typically, from 1 to 8 carbon atoms. Alkenyl groups may be substituted or unsubstituted. Alkenyl groups include, for instance, vinyl, propenyl, 2-butenyl, 3-butenyl, isobutenyl, cyclohexenyl, cyclopentenyl, cyclohexadienyl, butadienyl, pentadienyl, and hexadienyl groups among others. Alkenyl groups may be substituted similarly to alkyl groups. Divalent alkenyl groups, i.e., alkenyl groups with two points of attachment, include, but are not limited to, $\text{CH}=\text{CH}$, $\text{C}=\text{CH}$, or $\text{C}=\text{CHCH}$.

[0027] As used herein, “aryl”, or “aromatic,” groups are cyclic aromatic hydrocarbons that do not contain heteroatoms. Aryl groups include monocyclic, bicyclic and polycyclic ring systems. Thus, aryl groups include, but are not limited to, phenyl, azulenyl, heptalenyl, biphenylenyl, indacenyl, fluorenyl, phenanthrenyl, triphenylenyl, pyrenyl, naphthacenyl, chrysenyl, biphenyl, anthracenyl, indenyl, indanyl, pentalenyl, and naphthyl groups. In some embodiments, aryl groups contain 6-14 carbons, and in others from 6 to 12 or even 6-10 carbon atoms in the ring portions of the groups. The phrase “aryl groups” includes groups containing fused rings, such as fused aromatic-aliphatic ring systems (e.g., indanyl, tetrahydronaphthyl, and the like). Aryl groups may be substituted or unsubstituted.

[0028] It has been found that the electrochemical performance of lithium metal batteries (i.e. where the anode contains lithium metal, as a foil or sheet) is significantly improved where a short-chain terminally fluorinated glycol ether(s) is used in the electrolytes with an ionic liquid as compared to similar cells using non-fluorinated glycol ether(s) or even fluorinated glycol ether(s) with longer fluorinated alkyl chains. In some embodiments, the incorporation of a lithium fluorosulfonylimide salt coupled with the short-chain terminally fluorinated glycol ether provides a synergistic effect with regard to the stabilization of the lithium metal batteries, when compared to other batteries that include other salts (e.g. LiPF_6) or even the longer chain terminally fluorinated glycol ethers.

[0029] In one aspect, an electrochemical cell includes a cathode; an anode; and an electrolyte comprising a lithium salt, a terminally fluorinated glycol ether, an organosulfur solvent, and optionally an electrolyte additive, an aprotic gel polymer, or a mixture thereof. In some embodiments, the terminally fluorinated glycol ether is a short-chain terminally fluorinated glycol ether. In some embodiments, the organosulfur solvent is a fluorinated sulfone.

[0030] In one aspect, an electrochemical cell includes a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; and an electrolyte comprising a lithium fluorosulfonylimide salt, a terminally fluorinated glycol ether, and optionally an electrolyte additive, an aprotic gel polymer, or a mixture thereof. In some embodiments, the anode may further include silicon or a conductive carbon. In some embodiments, the terminally fluorinated glycol ether is a short-chain terminally fluorinated glycol ether.

[0031] In a further aspect, an electrochemical cell includes a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; a separator; and an electrolyte that includes a lithium fluorosulfonylimide salt, a terminally fluorinated glycol ether, an ionic liquid.

[0032] In any of the above aspects, the electrolyte may include at least a solvent and the salt, where the solvent includes the terminally fluorinated glycol ether. The solvent of the electrolyte may include greater than 50 wt % of the terminally fluorinated glycol ether. For example, the electrolyte may include greater than 75 wt % of the terminally fluorinated glycol ether, greater than 90 wt % of the terminally fluorinated glycol ether, or greater than 95 wt % of the terminally fluorinated glycol ether. In some embodiments, the solvent of the electrolyte is only a short-chain terminally

fluorinated glycol ether. In some embodiments, the electrolyte consists essentially of the lithium sulfonylimide salt, the terminally fluorinated glycol ether, and optionally the electrolyte additive. [0033] In any of the above aspects, the fluorinated glycol ether is a compound represented by Formula I: $R^{sup.1}(O(CH_{sub.2})_{sub.m})_{sub.x}(O(CH_{sub.2})_{sub.n})_{sub.y}OR^{sup.2}$ (I). In Formula I, $R^{sup.1}$ is a fluorinated alkyl; $R^{sup.2}$ is a fluorinated alkyl; m and n are each independently 1, 2, or 3; and x and y are independently 0, 1, 2, 3, with the proviso that both x and y are not 0 and $x+y \leq 3$. In some embodiments, one of $R^{sup.1}$ and $R^{sup.2}$ is a fluorinated alkyl having at least two fluorine atoms. In some embodiments, one of $R^{sup.1}$ and $R^{sup.2}$ is a fluorinated alkyl having at least three fluorine atoms.

[0034] In some embodiments, $R^{sup.1}$ is —

$(CH_{sub.2})_{sub.q}(CR^{sup.4}R^{sup.5})_{sub.p}C(R^{sup.3})_{sub.3}$; $R^{sup.2}$ is —

$(CH_{sub.2})_{sub.v}(CR^{sup.4'}R^{sup.5'})_{sub.w}C(R^{sup.3})_{sub.3}$; $R^{sup.3}$, $R^{sup.4}$, and $R^{sup.5}$ are each independently H or F, with the proviso that at least one of $R^{sup.3}$, $R^{sup.4}$, and $R^{sup.5}$ is F;

$R^{sup.3'}$, $R^{sup.4'}$, and $R^{sup.5'}$ are each independently H or F, with the proviso that at least one of $R^{sup.3'}$, $R^{sup.4'}$, and $R^{sup.5'}$ is F; q is 0, 1, 2, or 3; v is 0, 1, 2, or 3; p is 0, 1, 2, 3, 4, 5, or 6; and w is 0, 1, 2, 3, 4, 5, or 6. In some embodiments, $R^{sup.3}$ is F; $R^{sup.4}$ and $R^{sup.5}$ are H; q is 1 or 2; and p is 0. In some embodiments, $R^{sup.3'}$ is F; $R^{sup.4'}$ and $R^{sup.5'}$ are H; v is 1 or 2; and w is 0.

[0035] In some embodiments, $R^{sup.1}$ is —

$(CH_{sub.2})_{sub.q}(CR^{sup.4}R^{sup.5})_{sub.p}C(R^{sup.3})_{sub.3}$; $R^{sup.2}$ is —

$(CH_{sub.2})_{sub.v}(CR^{sup.4'}R^{sup.5'})_{sub.w}C(R^{sup.3'})_{sub.3}$; $R^{sup.3}$, $R^{sup.4}$, and $R^{sup.5}$ are each independently H or F, with the proviso that at least one of $R^{sup.3}$, $R^{sup.4}$, and $R^{sup.5}$ is F;

$R^{sup.3'}$, $R^{sup.4'}$, and $R^{sup.5'}$ are each independently H or F, with the proviso that at least one of $R^{sup.3'}$, $R^{sup.4'}$, and $R^{sup.5'}$ is F; y is 0; x is 2 or 3; q is 0, 1, 2, or 3; v is 0, 1, 2, or 3; p is 0, 1, 2, 3, 4, 5, or 6; and w is 0, 1, 2, 3, 4, 5, or 6. In some embodiments, y is 0; and x is 2 or 3. In some

embodiments, $R^{sup.1}$ is — $(CH_{sub.2})_{sub.q}(CH_{sub.2})_{sub.p}C(R^{sup.3})_{sub.3}$; $R^{sup.2}$ is —

$(CH_{sub.2})_{sub.v}(CH_{sub.2})_{sub.w}C(R^{sup.3'})_{sub.3}$; q is 1; v is 1; p is 0; w is 0; $R^{sup.3}$ is F; $R^{sup.3'}$ is F; y is 0; x is 2 or 3; and m is 2.

[0036] In some embodiments, m is 1. In some embodiments, m is 2. In some embodiments, m is 3.

In some embodiments, n is 1. In some embodiments, n is 2. In some embodiments, n is 3.

[0037] In some embodiments, x is 0. In some embodiments, x is 1. In some embodiments, x is 2. In some embodiments, x is 3. In some embodiments, y is 0. In some embodiments, y is 1. In some embodiments, y is 2. In some embodiments, y is 3.

[0038] In some embodiments, q is 0. In some embodiments, q is 1. In some embodiments, q is 2. In some embodiments, q is 3. In some embodiments, p is 0. In some embodiments, p is 1. In some embodiments, p is 2. In some embodiments, p is 3. In some embodiments, p is 4. In some embodiments, p is 5. In some embodiments, p is 6.

[0039] In some embodiments, v is 0. In some embodiments, v is 1. In some embodiments, v is 2. In some embodiments, v is 3. In some embodiments, w is 0. In some embodiments, w is 1. In some embodiments, w is 2. In some embodiments, w is 3. In some embodiments, w is 4. In some embodiments, w is 5. In some embodiments, w is 6.

[0040] In some embodiments, $R^{sup.3}$ is H. In some embodiments, $R^{sup.3}$ is F. In some embodiments, $R^{sup.4}$ is H. In some embodiments, $R^{sup.4}$ is F. In some embodiments, $R^{sup.5}$ is H. In some embodiments, $R^{sup.5}$ is F.

[0041] In some embodiments, $R^{sup.3'}$ is H. In some embodiments, $R^{sup.3'}$ is F. In some embodiments, $R^{sup.4'}$ is H. In some embodiments, $R^{sup.4'}$ is F. In some embodiments, $R^{sup.5'}$ is H. In some embodiments, $R^{sup.5'}$ is F.

[0042] Illustrative examples of the short-chain terminally fluorinated glycol ether(s) include one or more of:

##STR00002##

[0043] Ionic liquids are materials that have both a cationic group and an anionic group, and which

are liquids at room temperature. In any of the above aspects, and generally, ionic liquids may include salts such as pyrrolidinium-based ionic liquids or imidazolium-based ionic liquids. Illustrative ionic liquids may be represented by a compound represented by one of Formula (I), Formula (II), or a mixture of any two or more thereof:

##STR00003##

[0044] In the above formulae, R^{sup.10}, R^{sup.11}, and R^{sup.12} are individually H, alkyl, or OR^{sup.24}; R^{sup.13} to R^{sup.23} are individually H, F, Cl, Br, I, OR^{sup.24}, alkyl, alkenyl, alkynyl, aryl, aralkyl, heterocyclyl, heterocyclalkyl, cycloalkyl, cycloalkylalkyl, —C(O)R^{sup.24}, —C(O)OR^{sup.24}, or —OC(O)R^{sup.25} where each R^{sup.24} is individually H or alkyl; each R^{sup.25} is individually H or alkyl; and each A^{sup.—} individually is a counterion (counter anion). In some embodiments, the ionic liquid may include a compound represented by Formula (I). In other embodiments, the ionic liquid may include a compound represented by Formula (II).

[0045] In some embodiments, R^{sup.10}, R^{sup.11}, and R^{sup.12} are individually H, C_{sub.1} to C_{sub.6} alkyl, or OR^{sup.24} where R^{sup.24} is C_{sub.1} to C_{sub.6} alkyl; and R^{sup.13} to R^{sup.23} are individually H or C_{sub.1} to C_{sub.6} alkyl. In some embodiments, R^{sup.10}, R^{sup.11}, and R^{sup.12} are individually H; and R^{sup.13} to R^{sup.23} are individually H, methyl, ethyl, propyl, or butyl. In other embodiments, R^{sup.10}, R^{sup.11}, and R^{sup.12} are individually H, methyl, ethyl, propyl, butyl, methoxy, ethoxy, n-propoxy, iso-propoxy, n-butyl, sec-butyl, iso-butyl, or tert-butyl; and R^{sup.13} to R^{sup.23} are individually H, methyl, ethyl, propyl, or butyl. In any such embodiments, the ionic liquid may be a salt of N-methyl-N-propylpyrrolidinium, N-methyl-N-butylpyrrolidinium, 1-ethyl-3-methylimidazolium, or 1-methoxyethyl-3-methylpyrrolidinium.

[0046] In Formulas (I) and (II), A^{sup.—} is a counterion (anion) for the cationic nitrogen residues. Illustrative A^{sup.—} counterions include, but are not limited to, N(SO_{sub.2}F)_{sub.2}^{sup.—}, N(SO_{sub.2}CF_{sub.3})_{sub.2}^{sup.—}, N(SO_{sub.2}C_{sub.2}F_{sub.5})_{sub.2}^{sup.—}, CF_{sub.3}SO_{sub.2}NSO_{sub.2}F_{sub.5}^{sup.—}, C_{sub.2}F_{sub.5}SO_{sub.2}NSO_{sub.2}CF_{sub.3}^{sup.—}, 4,5-dicyano-2-(trifluoromethyl)imidazole, 4,5-dicyano-2-methylimidazole, alkyl fluorophosphate, alkyl fluoroborate, 2,2',2''-tris(trifluoromethyl)benzotris(imidazolate), N(CN)_{sub.2}^{sup.—}, SO_{sub.4}^{sup.—}, NO_{sub.3}^{sup.—}, C(CF_{sub.3}SO_{sub.2})_{sub.3}^{sup.—}, ClO_{sub.4}^{sup.—}, BF_{sub.4}^{sup.—}, AsF_{sub.6}^{sup.—}, SbF_{sub.6}^{sup.—}, AlCl_{sub.4}^{sup.—}, PF_{sub.6}^{sup.—}, OH^{sup.—}, BF_{sub.2}(C_{sub.2}O_{sub.4})_{sub.2}^{sup.—}, B(C_{sub.2}O_{sub.4})_{sub.2}^{sup.—}, PF_{sub.2}(C_{sub.2}O_{sub.4})_{sub.2}^{sup.—}, PF_{sub.4}(C_{sub.2}O_{sub.4})_{sub.2}^{sup.—}, B_{sub.12}X_{sub.12}-pH_{sub.p}^{sup.—}, B_{sub.10}X_{sub.10}-pH_{sub.p}^{sup.—}, or a mixture of any two or more thereof, wherein X is independently at each occurrence F, Cl, Br, or I, p is 0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, or 12, and p' is 0, 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10. In some embodiments, the salt may be a bis(fluorosulfonyl)imide salt. For example, in some such embodiments, the ionic liquid may include N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide, N-methyl-N-butylpyrrolidinium bis(fluorosulfonyl)imide, 1-ethyl-3-methylimidazolium bis(fluorosulfonyl)imide, 1-methoxyethyl-3-methylpyrrolidinium bis(fluorosulfonyl)imide, or a mixture of any two or more thereof.

[0047] In any of the above aspects, the lithium sulfonylimide salt includes LiN(SO_{sub.2}F)_{sub.2}; LiN(SO_{sub.2}CF_{sub.3})_{sub.2}; LiN(SO_{sub.2}C_{sub.2}F_{sub.5})_{sub.2}; Li(SO_{sub.2}F)N(SO_{sub.2}CF_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}CH_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}C_{sub.2}H_{sub.5}); Li(SO_{sub.2}F)N(SO_{sub.2}C_{sub.2}F_{sub.5}); Li(SO_{sub.2}F)N(SO_{sub.2}CHF_{sub.2}); Li(SO_{sub.2}F)N(SO_{sub.2}CH_{sub.2}F); Li(SO_{sub.2}F)N(SO_{sub.2}CH_{sub.2}CF_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}CH_{sub.2}CHF_{sub.2}); Li(SO_{sub.2}F)N(SO_{sub.2}CHFCH_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}CHFCH_{sub.2}F); Li(SO_{sub.2}F)N(SO_{sub.2}CF_{sub.2}CH_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}CF_{sub.2}CF_{sub.3}); Li(SO_{sub.2}F)N(SO_{sub.2}CHFCH_{sub.2}); Li(SO_{sub.2}F)N(SO_{sub.2}CHFCH_{sub.2}F); Li(SO_{sub.2}F)N(SO_{sub.2}CF_{sub.2}CH_{sub.2}F); Li(SO_{sub.2}F)N(SO_{sub.2}CF_{sub.2}CH_{sub.2}F); Li(SO_{sub.2}CF_{sub.3})N(SO_{sub.2}CH_{sub.3}); Li(SO_{sub.2}CF_{sub.3})N(SO_{sub.2}CHF_{sub.2});

Li(SO.sub.2 CF.sub.3)N(SO.sub.2CH.sub.2CF.sub.3); Li(SO.sub.2

CF.sub.3)N(SO.sub.2CH.sub.2CF.sub.3), or a mixture of any two or more thereof. In some embodiments, the lithium sulfonylimide salt includes LiFSI.

[0048] The electrochemical cells described herein may also include in the electrolytes, an electrolyte stabilizing additive that may be LiBF.sub.2(C.sub.2O.sub.4),

LiB(C.sub.2O.sub.4).sub.2, LiPF.sub.2(C.sub.2O.sub.4).sub.2, LiPF.sub.4(C.sub.2O.sub.4),

LiPF.sub.6, LiAsF.sub.6, CSF, CsPF.sub.6, Li.sub.2(B.sub.12X.sub.12-iH.sub.i),

Li.sub.2(B.sub.10X.sub.10-i'H.sub.i'), or a mixture of any two or more thereof. In such additives, each X is independently at each occurrence a halogen, i is an integer from 0 to 12 and i' is an integer from 0 to 10. In some embodiments, the electrolyte may also contain an electrode

stabilizing additive such as but not limited to LiB(C.sub.2O.sub.4).sub.2,

LiBF.sub.2(C.sub.2O.sub.4).sub.2, 1,3,2-dioxathiolane-2,2-dioxide, ethylene sulfite, a spirocyclic hydrocarbon containing at least one oxygen atom and at least one alkenyl or alkynyl group,

pyridazine, vinyl pyridazine, quinolone, pyridine, vinyl pyridine, 2,4-divinyl-tetrahydropyran, 3,9-diethylidene-2,4,8-trioxaspiro [5,5] undecane, 2-ethylidene-5-vinyl-[1,3] dioxane, anisoles, 2,5-dimethyl-1,4-dimethoxybenzene, 2,3,5,6-tetramethyl-1,4-dimethoxybenzene, 2,5-di-tert-butyl-1,4-dimethoxybenzene, or a mixture of two or more thereof. The electrolyte additive may be present at a concentration of less than about 5 wt %. The electrolyte additive may be present at a concentration of from about 0.01 wt % to about 5 wt %.

[0049] In further embodiments, the electrolyte may further include an aprotic gel polymer. For example, mixtures of poly(ethylene oxide) (PEO) with lithium salts and an organic aprotic solvent may be used.

[0050] In some embodiments, the electrolyte may also include a redox shuttle material. The shuttle, if present, will have an electrochemical potential above the positive electrode's maximum normal operating potential. Illustrative stabilizing agents include, but are not limited to, a spirocyclic hydrocarbon containing at least one oxygen atom and at least one alkenyl or alkynyl group, pyridazine, vinyl pyridazine, quinolone, pyridine, vinyl pyridine, 2,4-divinyl-tetrahydroopyran, 3,9-diethylidene-2,4,8-trioxaspiro [5,5]undecane, 2-ethylidene-5-vinyl-[1,3]dioxane, lithium alkyl fluorophosphates, lithium alkyl fluoroborates, lithium 4,5-dicyano-2-(trifluoromethyl)imidazole, lithium 4,5-dicyano-2-methylimidazole, trilithium 2,2',2''-

tris(trifluoromethyl)benzotris(imidazolate), Li(CF.sub.3CO.sub.2), Li(C.sub.2F.sub.5CO.sub.2), LiCF.sub.3SO.sub.3, LiCH.sub.3SO.sub.3, LiN(SO.sub.2CF.sub.3).sub.2,

LiC(CF.sub.3SO.sub.2).sub.3, LiN(SO.sub.2C.sub.2F.sub.5).sub.2, LiClO.sub.4, LiAsF.sub.6,

Li.sub.2(B.sub.12X.sub.12-iH.sub.i), Li.sub.2(B.sub.10X.sub.10-i'H.sub.i'), wherein X is independently at each occurrence a halogen, I is an integer from 0 to 12 and I' is an integer from 0 to 10, 1,3,2-dioxathiolane 2,2-dioxide, 4-methyl-1,3,2-dioxathiolane 2,2-dioxide, 4-

(trifluoromethyl)-1,3,2-dioxathiolane 2,2-dioxide, 4-fluoro-1,3,2-dioxathiolane 2,2-dioxide, 4,5-difluoro-1,3,2-dioxathiolane 2,2-dioxide, dimethyl sulfate, methyl (2,2,2-trifluoroethyl) sulfate, methyl (trifluoromethyl) sulfate, bis(trifluoromethyl) sulfate, 1,2-oxathiolane 2,2-dioxide, methyl ethanesulfonate, 5-fluoro-1,2-oxathiolane 2,2-dioxide, 5-(trifluoromethyl)-1,2-oxathiolane 2,2-dioxide, 4-fluoro-1,2-oxathiolane 2,2-dioxide, 4-(trifluoromethyl)-1,2-oxathiolane 2,2-dioxide, 3-fluoro-1,2-oxathiolane 2,2-dioxide, 3-(trifluoromethyl)-1,2-oxathiolane 2,2-dioxide, difluoro-1,2-oxathiolane 2,2-dioxide, 5H-1,2-oxathiole 2,2-dioxide, 2,5-dimethyl-1,4-dimethoxybenzene, 2,3,5,6-tetramethyl-1,4-dimethoxybenzene, 2,5-di-tert-butyl-1,4-dimethoxybenzene or a mixture of any two or more thereof, with the proviso that when used, the redox shuttle is not the same as the lithium salt, even though they perform the same function in the cell. That is, for example, if the lithium salt is LiClO.sub.4, it may also perform the dual function of being a redox shuttle, however if a redox shuttle is included in that same cell, it will be a different material than LiClO.sub.4. The electrolyte additive may be present in the electrolyte in an amount of about 1% to about 10% by weight or by volume. This includes an amount of about 1% to about 8% by weight or by volume,

about 1% to about 6% by weight or by volume, about 1% to about 4% by weight or by volume, or about 1% to about 3% by weight or by volume. In some embodiments, the electrolyte additive is present in the electrolyte in an amount of about 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10% by weight or by volume.

[0051] Also as noted herein, the electrolyte may further include electrolyte additives to help stabilize the electrode, assist in include, but are not limited to $\text{LiBF}_2(\text{C}_2\text{O}_4)$, $\text{LiB}(\text{C}_2\text{O}_4)_2$, $\text{LiPF}_2(\text{C}_2\text{O}_4)_2$, $\text{LiPF}_4(\text{C}_2\text{O}_4)$, LiPF_6 , LiAsF_6 , CsF , CsPF_6 , $\text{LiN}(\text{SO}_2\text{CF}_3)_2$, $\text{LiN}(\text{SO}_2\text{F})_2$, $\text{Li}_2(\text{B}_{12}\text{X}_{12}-i\text{H}_i)$; $\text{Li}_2(\text{B}_{10}\text{X}_{10}-i'\text{H}_{i'})$, or a mixture of any two or more thereof. As set forth, each X is independently a halogen, each i is an integer from 0 to 12 and each i' is an integer from 0 to 10. The electrolyte additive may be present at a concentration of about 5 wt % or less. For example, the electrolyte additive when present, may be present at a concentration of about 0.1 wt % to about 5 wt %, about 1 wt % to about 5 wt %, or about 0.5 wt % to about 3 wt %.

[0052] As noted above, the anode includes lithium metal. This may be present in the form of a foil, sheet, sand, or other metallic form. In some embodiments, the anode includes lithium metal foil. In addition, silicon or conductive carbon materials may be included in the anode. In some embodiments, the conductive carbon is carbon nanotubes, carbon fiber, microporous carbon, mesoporous carbon, macroporous carbon, mesoporous microbeads, graphite, expandable graphite, polymer yield carbon, or carbon black. The metal of the anode may be the current collector, or the anode may also include a current collector.

[0053] The electrochemical devices also include a cathode. The cathode may include oxygen (O_2), in some embodiments. In other embodiments, the cathode may include a metal oxide which may be, but is not limited to, a spinel, an olivine, a carbon-coated olivine LiFePO_4 , $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_2$, LiCoO_2 , LiNiO_2 , $\text{LiNi}_{1-x}\text{Co}_y\text{Me}_z\text{O}_2$, $\text{LiNi}_{\alpha}\text{Mn}_{\beta}\text{Co}_{\gamma}\text{O}_2$, LiMn_2O_4 , LiFeO_2 , $\text{LiNi}_{0.5}\text{Me}_{1.5}\text{O}_4$, $\text{Li}_{1+x'}\text{Ni}_h\text{Mn}_k\text{Co}_l\text{Me}_{\text{sup.2}}\text{O}_{2-z'}\text{F}_{z'}$, VO_2 , $\text{E}_{\text{sub.x''}}\text{E}'_{\text{sub.2}}(\text{Me}_{\text{sub.3}}\text{O}_4)_{\text{sub.3}}$, $\text{LiNi}_m\text{Mn}_n\text{O}_4$, wherein Me is Al, Mg, Ti, B, Ga, Si, Mn, or Co; $\text{Me}_{\text{sup.2}}$ is Mg, Zn, Al, Ga, B, Zr, or Ti; E is Li, Ag, Cu, Na, Mn, Fe, Co, Ni, or Zn; E' is Ti, V, Cr, Fe, or Zr; wherein $0 \leq x \leq 0.3$; $0 \leq y \leq 0.5$; $0 \leq z \leq 0.5$; $0 \leq m \leq 2$; $0 \leq n \leq 2$; $0 \leq x' \leq 0.4$; $0 \leq \alpha \leq 1$; $0 \leq \beta \leq 1$; $0 \leq \gamma \leq 1$; $0 \leq h \leq 1$; $0 \leq k \leq 1$; $0 \leq l \leq 1$; $0 \leq y' \leq 0.4$; $0 \leq z' \leq 0.4$; and $0 \leq x'' \leq 3$; with the proviso that at least one of h, k and l is greater than 0. In some embodiments, the metal oxide includes $\text{Li}_{1+w}\text{Mn}_x\text{Ni}_y\text{CO}_2\text{O}_2$ wherein w, x, y, and z satisfy the relations $0 < w < 1$, $0 \leq x < 1$, $0 \leq y < 1$, $0 \leq z < 1$, and $x+y+z=1$. In some embodiments, the metal oxide includes $\text{LiMn}_x\text{Ni}_y\text{O}_4$ wherein x and y satisfy the $0 \leq x < 2$, $0 \leq y < 2$, and $x+y=2$. In some embodiments, the positive electrode includes $\text{LiMn}_x\text{Ni}_y\text{O}_4$ wherein x and y satisfy the $0 \leq x < 2$, $0 \leq y < 2$, and $x+y=2$. In some embodiments, the positive electrode includes $x\text{Li}_{0.2}\text{MnO}_{0.3}\text{Math.}(1-x)\text{LiMO}_{0.2}$ is wherein $0 \leq x < 2$. In some embodiments, the cathode includes a metal oxide that is $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_2$, LiCoO_2 , LiNiO_2 , $\text{LiNi}_{1-x}\text{Co}_y\text{Mn}_2\text{O}_2$, or a combination of any two or more thereof. In one embodiment, the cathode includes a metal oxide that is LiCoO_2 (lithium cobalt oxide). In one embodiment, the cathode includes a metal oxide that is LiFePO_4 (lithium iron phosphate oxide (LFP)). In some embodiments, the metal oxide is a lithium nickel manganese cobalt oxide (NMC). For example, the cathode may include a metal oxide that is $\text{LiNi}_{\alpha}\text{Mn}_{\beta}\text{Co}_{\gamma}\text{O}_2$, NMC111 ($\text{LiNi}_{0.33}\text{CO}_{0.33}\text{Mn}_{0.33}\text{O}_2$), NMC532 ($\text{LiNi}_{0.5}\text{Co}_{0.2}\text{Mn}_{0.3}\text{O}_2$), NMC622 ($\text{LiNi}_{0.6}\text{Co}_{0.2}\text{Mn}_{0.2}\text{O}_2$), NMC811 ($\text{LiNi}_{0.8}\text{CO}_{0.1}\text{Mn}_{0.1}\text{O}_2$) or a Ni-rich layer material such as $\text{Li}_{1+x'}\text{Ni}_n\text{Mn}_k\text{Co}_l\text{Me}_{\text{sup.2}}\text{O}_{2-z'}\text{F}_{z'}$; where $0 \leq h \leq 1$. In some

embodiments, the cathode comprises $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_{0.5}\text{O}_{0.5}$, LiCoO_2 , LiNiO_2 , $\text{LiNi}_{1-x}\text{Co}_x\text{Mn}_y\text{O}_z$, or a combination of any two or more thereof, wherein $0 \leq x \leq 0.3$; $0 \leq y \leq 0.5$; $0 \leq z \leq 0.5$.

[0054] The term “spinel” refers to a manganese-based spinel such as, $\text{Li}_{1+x}\text{Mn}_{2-y}\text{Me}_z\text{O}_{4-h}\text{A}_k$, wherein Me is Al, Mg, Ti, B, Ga, Si, Ni, or Co; A is S or F; and wherein $0 \leq x \leq 0.5$, $0 \leq y \leq 0.5$, $0 \leq z \leq 0.5$, $0 \leq h \leq 0.5$, and $0 \leq k \leq 0.5$.

[0055] The term “olivine” refers to an iron-based olivine such as, $\text{LiFe}_{1-x}\text{Me}_y\text{PO}_4\text{A}_k$, wherein Me is Al, Mg, Ti, B, Ga, Si, Ni, or Co; A is S or F; and wherein $0 \leq x \leq 0.5$, $0 \leq y \leq 0.5$, $0 \leq h \leq 0.5$, and $0 \leq k \leq 0.5$.

[0056] The cathode may be further stabilized by surface coating the active particles with a material that can neutralize acid or otherwise lessen or prevent leaching of the transition metal ions. Hence, the cathodes may also include a surface coating of a metal oxide or fluoride such as ZrO_2 , TiO_2 , ZnO , WO_3 , Al_2O_3 , MgO , SiO_2 , SnO_2 , AlPO_4 , $\text{Al}(\text{OH})_3$, AlF_3 , ZnF_2 , MgF_2 , TiF_4 , ZrF_4 , a mixture of any two or more thereof, of any other suitable metal oxide or fluoride. The coating can be applied to a carbon coated cathode.

[0057] The cathode may be further stabilized by surface coating the active particles with polymer materials. Examples of polymer coating materials include, but not limited to, polysiloxanes, polyethylene glycol, or poly(3,4-ethylenedioxythiophene) polystyrene sulfonate, a mixture of any two or more polymers.

[0058] The electrodes of the electrochemical cells (i.e. the lithium batteries) may also include a current collector. Current collectors for either the anode or the cathode may include those of copper, stainless steel, titanium, tantalum, platinum, gold, aluminum, nickel, cobalt, cobalt nickel alloy, highly alloyed ferritic stainless steel containing molybdenum and chromium; or nickel-, chromium-, or molybdenum containing alloys.

[0059] The electrodes (i.e., the cathode and/or the anode) may also include a conductive polymer as a binder. Illustrative conductive polymers include, but not limited to, polyaniline, polypyrrole, poly(pyrrole-co-aniline), polyphenylene, polythiophene, polyacetylene, polysiloxane, polyvinylidene difluoride, or polyfluorene.

[0060] The electrochemical cells disclosed herein may also include a porous separator to separate the cathode from the anode and prevent, or at least minimize, short-circuiting in the device. The separator may be a polymer or ceramic or mixed separator. The separator may include, but is not limited to, polypropylene (PP), polyethylene (PE), trilayer (PP/PE/PP), or polymer films that may optionally be coated with alumina-based ceramic particles. In some embodiments, the separator is an aluminum oxide-filled polyolefin. In other embodiments, the separator is an aluminum oxide-filled polypropylene.

[0061] As an example of the electrochemical cells described herein are lithium secondary batteries. The lithium secondary batteries described herein may find application as a lithium battery or a lithium-air battery.

[0062] The present invention, thus generally described, will be understood more readily by reference to the following examples, which are provided by way of illustration and are not intended to be limiting of the present invention.

EXAMPLES

[0063] Example 1. A $\text{Li} \parallel \text{Li}$ symmetric cell was prepared by is assembled with lithium metal as both counter and reference electrode in an argon atmosphere glovebox (≤ 1 ppm of O_2 and H_2O). The charging/discharging rate was 2 mAh cm^{-2} . The electrolyte was (A) 1.2 M LiPF_6 in a terminally fluorinated diethylene glycol ether (FDG, 100%) and (B) a mixture of 1.2M LiPF_6 in a 3:7 (wt/wt) ratio of ethylene carbonate to ethylmethyl carbonate (“Gen2”). For clarity, the structure of terminally fluorinated diethylene glycol ether (FDG) used is:

##STR00004##

[0064] Example 2. Cycling of the cells prepared in Example 1. The cells prepared above in Example 1 were cycled at a current density of 2 mAcm^{sup.2}. As illustrated in FIG. 1, the charge/discharge voltage stabilized within ± 0.5 V for the cells using the 1.2M LiPF_{sub.6} in FDG electrolyte (A), while the charge/discharge voltages for conventional 1.2M LiPF_{sub.6} in EC/EMC (Gen2) electrolyte was large ($>\pm 1.5$ V) and highly fluctuating. These results clearly show that electrolyte (A) enables a much more stable lithium plating and stripping than the Gen2 electrolyte.

[0065] Example 3. Li||Li symmetric cells were prepared as in Example 1, but with (A) 1.2M LiPF_{sub.6} in FDG, and (B) 1.2M LiPF_{sub.6} in terminally fluorinated tetraethylene glycol ether (FTEG), i.e. a longer-chain terminally fluorinated glycol ether than FDG, and (C) lithium bis(fluoromethanesulfonyl)imide (LiFSI) in FDG in a LiFSI:FDG molar ratio of 1:3 (this equates to approximately 2 M). This example illustrates the stability difference when the PF_{sub.6} salt is used compared to the fluorinated sulfonylimide.

##STR00005##

[0066] Example 4. Cycling of the cells prepared in Example 3. The cells prepared above in Example 3 were cycled at a current density of 2 mAcm^{sup.2}. As illustrated in FIG. 2 a graph of cycling performance is provided for the cells using the different electrolytes. The cycling performance of the cell using the FDG was clearly superior to that of the cell using FTEG, of which the charge/discharge voltages were large and highly fluctuating. More importantly, the charge/discharge voltage of the Li||Li cell using electrolyte (C) LiFSI:FDG 1:3 molar ratio was highly stable with charge/discharge voltage stabilized within ± 0.1 V after 20 cycles, demonstrating the synergistic effect of LiFSI salt and short chain terminally fluorinated glycol ether.

[0067] Example 5. Li||Li symmetric cells were prepared as in Example 1, but with LiFSI in FDG (1:3 molar ratio) and 1M LiTFSI in FDG. The cells were then cycled at a current density of 2 mAcm^{sup.2}. As illustrated in FIG. 3 a graph of cycling performance is provided for the cells using the two different electrolytes. The cycling performance of the Li||Li cell using LiTFSI-based electrolyte with FDG solvent was clearly better than Li||Li cell using LiPF_{sub.6} based electrolyte as evidenced by the smaller charge/discharge voltage fluctuation. The cycling performance of the cell using LiFSI in FDG was clearly superior to both the cells using LiPF_{sub.6} and LiTFSI based electrolytes, however, LiTFI may find use as a co-salt with the LFSI.

[0068] Example 6. 2032 coin cells of Li||NMC811 (LiNi_{sub.0.8}Mn_{sub.0.1}Co_{sub.0.1}O_{sub.2}) were prepared with an NMC811 positive electrode (1.93 mAh cm^{sup.-2} areal capacity), a foil of Li metal anode, one piece of separator (Celgard 2325), and the prepared electrolyte (30 μ L in each cell). The Li||NMC811 cells were prepared in an argon atmosphere glovebox (≤ 1 ppm of O_{sub.2} and H_{sub.2}O). The electrolytes included those as used in Examples 1 and 3 as Gen2 and (C); as well as LiFSI in (E) one-sided terminally fluorinated diethylene glycol ether (1-FDG), (F) diglyme (DG), and (G) longer chain terminally fluorinated tetraethylene glycol ether (FTEG) using an 1:3 molar ratio. The coin cells were cycled between 2.5 V to 4.3 V. As depicted in FIGS. 4A and 4B, the cycling performance of the Li||NMC811 cells illustrates that the capacity of the cell with the conventional ("Gen2") electrolyte decayed rapidly within 60 cycles due to lithium dendrite formation. Meanwhile, the cell employing non-fluorinated DG electrolyte displayed relatively low specific capacity and Coulombic efficiency with fast capacity fading. Moreover, the Li||NMC811 cell using longer chain terminally fluorinated tetraethylene glycol ether (FTEG) presented even lower specific capacity and Coulombic efficiency than the DG cell, while the Li||NMC811 cell employing one-sided terminally fluorinated diethylene glycol ether (1-FDG) electrolyte showed enhanced specific capacity, capacity retention, and Coulombic efficiency. This indicates that there is a synergistic effect of lithium fluorosulfonylimide salt with short-chain terminally fluorinated glycol ethers. Further, the cell using short chain terminally fluorinated diethylene glycol ether (FDG) with fluorinated group at both terminals displayed the best cycling performance with exceptional capacity retention and Coulombic efficiency.

[0069] Example 7. 2032 coin cells of Li||NMC811 were prepared as in Example 6, but with operational voltage between 3.0 V to 4.4 V. With a higher upper cutoff voltage, the difference in cycling performance was amplified. As displayed in FIGS. 5A and 5B, the capacity of Li||NMC811 cell using conventional electrolyte Gen2 dropped rapidly to $\leq 20\%$ within 70 cycles. The rate of capacity fade for the cell using non-fluorinated DG based electrolyte was significantly enhanced. The specific capacity of the Li||NMC811 cell employing FTeG electrolyte dropped below 100 mAh/g within the 10 cycles, which again demonstrated the ineffectiveness of longer chain terminally fluorinated glycol ether. Comparatively, the Li||NMC811 cell using the one-sided terminally fluorinated diethylene glycol ether (1-FDG) electrolyte again exhibited enhanced specific capacity, capacity retention, and Coulombic efficiency, while the cell using short chain terminally fluorinated diethylene glycol ether (FDG) with fluorinated group at both terminals displayed the best cycling performance again. These results clearly support the synergistic effect of lithium fluorosulfonylimide salt with a short-chain terminally fluorinated glycol ether.

[0070] The electrochemical performance of the lithium battery using a short-chain terminally fluorinated glycol ether as the electrolyte solvent is significantly better than those cells using an unfluorinated glycol ether or a fluorinated glycol ether with a longer chain length. In addition, the use of a lithium fluorosulfonylimide salt (e.g., LiFSI) coupled with a short-chain terminally fluorinated glycol ether offers a profound synergistic effect on the stabilization of lithium metal batteries.

[0071] Example 8. Li||Li symmetric cells were assembled with lithium metal as both the counter and reference electrode with a glass fiber separator, and electrolyte (50 μ L in each cell). The Li||Li cells were prepared in an argon atmosphere glovebox (≤ 1 ppm of O₂ and H₂O). Different cells has different electrolytes. The electrolytes included:

[0072] Cell A: 2M lithium

bis(fluoromethanesulfonyl)imide (LiFSI) dissolved in N-methyl-N-propylpyrrolidinium

bis(fluorosulfonyl)imide ("Py13 FSI"). [0073] Cell B: 2M LiFSI in Py13 FSI and 1,1,2,2-

tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether (TTE) in a Py13 FSI:TTE volume ratio of 1:4.

[0074] Cell C: 2M LiFSI dissolved in Py13 FSI and terminally fluorinated diethylene glycol ether

(1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane (FDG) in a Py13 FSI:FDG

volume ratio of 1:4. [0075] Cell D: 1.2M lithium hexafluorophosphate (LiPF₆) dissolved in

ethylene carbonate (EC):ethyl methyl carbonate (EMC) in a 3:7 weight ratio.

[0076] Cycling of the cells prepared in Example 8. The cells were cycled at a current density of 2 mA/cm². As illustrated in FIG. 6, the charge/discharge voltage stabilized within ± 0.1 V for Cells B and C, while the charge/discharge voltages for Cell D was highly fluctuating and large ($> \pm 0.5$ V within 40 hours of cycling). The fluctuation of Cell A was smaller than that of Cell D but larger than Cells B and C. These results show that the ionic liquid electrolytes with the fluorinated ether or glycol ether co-solvents provides for more stable lithium plating and stripping, compared to the conventional electrolytes or pure ionic liquid electrolytes.

[0077] Example 9. 2032 coin cells of lithium (Li) |NMC811

(LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂) were prepared with an NMC811 positive electrode

(1.43 mAh/cm² areal capacity), a lithium metal anode, a separator, and an electrolyte (50 μ L

in each cell). The Li||NMC811 cells were prepared in an argon atmosphere glovebox (≤ 1 ppm of

O₂ and H₂O). The electrolyte was 2M lithium bis(fluoromethanesulfonyl)imide (LiFSI)

dissolved in Py13 FSI. The separator used was a glass fiber separator (Cell E) and an aluminum

oxide-filled polyolefin separator (Cell F).

[0078] Cycling of the cells prepared in Example 9. Cells E and F were cycled between 3.0 V to 4.3

V at a rate of C/2. As illustrated in FIG. 7, the cycling performance of the Li||NMC811 cells

illustrates that Cell F with an aluminum oxide-filled polyolefin separator displayed significantly

improved Coulombic efficiency, compared to the cycling performance of Cell E using glass fiber

separator.

[0079] Example 10. 2032 coin cells of lithium (Li)||NMC811 (LiNi_{0.8}Mn_{0.1}Co_{0.1}O₂) were prepared with an NMC811 positive electrode (1.43 mAh cm^{sup}.-2 areal capacity), a lithium metal anode, a aluminum oxide-filled polyolefin separator, and an electrolyte (50 μ L in each cell). The Li||NMC811 cells were prepared in an argon atmosphere glovebox (≤ 1 ppm of O₂ and H₂O). The electrolytes included: [0080] Cell G: 2M LiFSI dissolved in Py13 FSI. [0081] Cell H: 2M LiFSI in Py13 FSI and TTE in a Py13 FSI:TTE volume ratio of 1:4. [0082] Cell I: 2M LiFSI dissolved in Py13 FSI and FDG in a Py13 FSI:FDG volume ratio of 1:4.

[0083] The cells were cycled between 3.0 V to 4.3 V. As depicted in FIG. 8A, Cell H displayed enhanced cycling performance compared to Cell G, and Cell I presented the best capacity retention and a largely elongated cycle life, suggesting the use of FDG in Py13 FSI ionic liquid generated a significant synergistic effect. As depicted in FIG. 8B, Cells H and I showed a significantly higher average Coulombic efficiency than Cell G, further supporting the synergistic effect of fluorinated ether or glycol ether with ionic liquid electrolyte. The Coulombic efficiency of Cell H was the most stable.

[0084] The 1st-cycle voltage profiles for Cells G, H, and are shown in FIG. 9. As illustrated, a slightly larger polarization was observed for Cell G compared to Cell H, suggesting the stronger solvating ability of FDG, which leads to higher electrolyte conductivity and lower cell impedance.

[0085] The 50^{sup}.th-cycle voltage profiles for Cells G and I are shown in FIG. 10. A significantly larger polarization was observed for Cell G compared to Cell I, suggesting the faster resistance built up on Cell G. This result showed again the large synergistic effect between terminally fluorinated glycol ether and ionic liquid electrolyte.

[0086] While certain embodiments have been illustrated and described, it should be understood that changes and modifications can be made therein in accordance with ordinary skill in the art without departing from the technology in its broader aspects as defined in the following claims.

[0087] The embodiments, illustratively described herein may suitably be practiced in the absence of any element or elements, limitation or limitations, not specifically disclosed herein. Thus, for example, the terms “comprising,” “including,” “containing,” etc. shall be read expansively and without limitation. Additionally, the terms and expressions employed herein have been used as terms of description and not of limitation, and there is no intention in the use of such terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the claimed technology. Additionally, the phrase “consisting essentially of” will be understood to include those elements specifically recited and those additional elements that do not materially affect the basic and novel characteristics of the claimed technology. The phrase “consisting of” excludes any element not specified.

[0088] The present disclosure is not to be limited in terms of the particular embodiments described in this application. Many modifications and variations can be made without departing from its spirit and scope, as will be apparent to those skilled in the art. Functionally equivalent methods and compositions within the scope of the disclosure, in addition to those enumerated herein, will be apparent to those skilled in the art from the foregoing descriptions. Such modifications and variations are intended to fall within the scope of the appended claims. The present disclosure is to be limited only by the terms of the appended claims, along with the full scope of equivalents to which such claims are entitled. It is to be understood that this disclosure is not limited to particular methods, reagents, compounds compositions or biological systems, which can of course vary. It is also to be understood that the terminology used herein is for the purpose of describing particular embodiments only, and is not intended to be limiting.

[0089] In addition, where features or aspects of the disclosure are described in terms of Markush groups, those skilled in the art will recognize that the disclosure is also thereby described in terms of any individual member or subgroup of members of the Markush group.

[0090] As will be understood by one skilled in the art, for any and all purposes, particularly in terms of providing a written description, all ranges disclosed herein also encompass any and all possible subranges and combinations of subranges thereof. Any listed range can be easily recognized as sufficiently describing and enabling the same range being broken down into at least equal halves, thirds, quarters, fifths, tenths, etc. As a non-limiting example, each range discussed herein can be readily broken down into a lower third, middle third and upper third, etc. As will also be understood by one skilled in the art all language such as “up to,” “at least,” “greater than,” “less than,” and the like, include the number recited and refer to ranges which can be subsequently broken down into subranges as discussed above. Finally, as will be understood by one skilled in the art, a range includes each individual member.

[0091] All publications, patent applications, issued patents, and other documents referred to in this specification are herein incorporated by reference as if each individual publication, patent application, issued patent, or other document was specifically and individually indicated to be incorporated by reference in its entirety. Definitions that are contained in text incorporated by reference are excluded to the extent that they contradict definitions in this disclosure.

[0092] Other embodiments are set forth in the following claims.

Claims

1. An electrochemical cell comprising: a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; a separator; and an electrolyte comprising: a lithium fluorinated sulfonylimide salt; a terminally fluorinated glycol ether of Formula (I)

$R_{sup.1}(O(CH_{sub.2})_{sub.m})_{sub.x}(O(CH_{sub.2})_{sub.n})_{sub.y}OR_{sup.2}$ (I); and an ionic liquid; wherein: $R_{sup.1}$ is a fluorinated alkyl; $R_{sup.2}$ is a fluorinated alkyl; m is 1, 2, or 3; n is 1, 2, or 3; and x and y are each independently 0, 1, or 2, with the provisos that both x and y are not 0 and $x+y \leq 3$.

2. The electrochemical cell of claim 1, wherein $R_{sup.1}$ is —

$(CH_{sub.2})_{sub.q}(CR_{sup.4}R_{sup.5})_{sub.p}C(R_{sup.3})_{sub.3}$; $R_{sup.2}$ is —

$(CH_{sub.2})_{sub.v}(CR_{sup.4'}R_{sup.5'})_{sub.w}C(R_{sup.3'})_{sub.3}$; $R_{sup.3}$, $R_{sup.4}$, and $R_{sup.5}$ are each independently H or F, with the proviso that at least one of $R_{sup.3}$, $R_{sup.4}$, and $R_{sup.5}$ is F; $R_{sup.3'}$, $R_{sup.4'}$, and $R_{sup.5'}$ are each independently H or F, with the proviso that at least one of $R_{sup.3'}$, $R_{sup.4'}$, and $R_{sup.5'}$ is F; q is 0, 1, 2, or 3; p is 0, 1, 2, 3, 4, 5, or 6; v is 0, 1, or 2; and w is 0, 1, 2, 3, 4, 5, or 6.

3. The electrochemical cell of claim 2, wherein $R_{sup.3}$ is F; $R_{sup.4}$ and $R_{sup.5}$ are H; q is 1 or 2; p is 0; y is 0; and x is 2.

4. The electrochemical cell of claim 1, wherein the terminally fluorinated glycol ether is 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof.

5. The electrochemical cell of claim 1, wherein the ionic liquid comprises a compound represented by Formula (I), Formula (II), or a mixture of any two or more thereof: ##STR00006## wherein: $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually H, alkyl, or $OR_{sup.24}$; $R_{sup.13}$ to $R_{sup.23}$ are individually H, F, Cl, Br, I, $OR_{sup.24}$, alkyl, alkenyl, alkynyl, aryl, aralkyl, heterocyclyl, heterocyclylalkyl, cycloalkyl, cycloalkylalkyl, $-C(O)R_{sup.24}$, $-C(O)OR_{sup.24}$, or $-OC(O)R_{sup.25}$ where each $R_{sup.24}$ is individually H or alkyl and each $R_{sup.25}$ is individually H or alkyl; and each $A_{sup.-}$ individually is a counterion (counter anion).

6. The electrochemical cell of claim 5, wherein the ionic liquid is a compound represented by Formula (I).

7. The electrochemical cell of claim 5, wherein the ionic liquid is a compound represented by Formula (II).

8. The electrochemical cell of claim 5, wherein $R_{sup.10}$, $R_{sup.11}$, and $R_{sup.12}$ are individually

H, C.sub.1 to C.sub.6 alkyl, or OR.sup.24 where R.sup.24 is C.sub.1 to C.sub.6 alkyl; and R.sup.13 to R.sup.23 are individually H or C.sub.1 to C.sub.6 alkyl.

9. The electrochemical cell of claim 5, wherein R.sup.10, R.sup.11, and R.sup.12 are individually H; and R.sup.13 to R.sup.23 are individually H, methyl, ethyl, propyl, or butyl.

10. The electrochemical cell of claim 5, wherein the ionic liquid is a salt of N-methyl-N-propylpyrrolidinium, N-methyl-N-butylpyrrolidinium, 1-ethyl-3-methylimidazolium, or 1-methoxyethyl-3-methylpyrrolidinium.

11. The electrochemical cell of claim 10, wherein the ionic liquid is N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide, N-methyl-N-butylpyrrolidinium bis(fluorosulfonyl)imide, 1-ethyl-3-methylimidazolium bis(fluorosulfonyl)imide, 1-methoxyethyl-3-methylpyrrolidinium bis(fluorosulfonyl)imide, or a mixture of any two or more thereof.

12. The electrochemical cell of claim 1, wherein the lithium fluorinated sulfonylimide salt comprises LiN(SO.sub.2F).sub.2; LiN(SO.sub.2CF.sub.3).sub.2;

LiN(SO.sub.2C.sub.2F.sub.5).sub.2; Li(SO.sub.2F)N(SO.sub.2CF.sub.3);

Li(SO.sub.2F)N(SO.sub.2CH.sub.3); Li(SO.sub.2F)N(SO.sub.2C.sub.2H.sub.5);

Li(SO.sub.2F)N(SO.sub.2C.sub.2F.sub.5); Li(SO.sub.2F)N(SO.sub.2CHF.sub.2);

Li(SO.sub.2F)N(SO.sub.2CH.sub.2F); Li(SO.sub.2F)N(SO.sub.2CH.sub.2CF.sub.3);

Li(SO.sub.2F)N(SO.sub.2CH.sub.2CHF.sub.2); Li(SO.sub.2F)N(SO.sub.2CHFCH.sub.3);

Li(SO.sub.2F)N(SO.sub.2CHFCH.sub.3); Li(SO.sub.2F)N(SO.sub.2CHFCHF.sub.2);

Li(SO.sub.2F)N(SO.sub.2CHFCH.sub.2F); Li(SO.sub.2F)N(SO.sub.2CF.sub.2CH.sub.3);

Li(SO.sub.2F)N(SO.sub.2CF.sub.2CF.sub.3); Li(SO.sub.2F)N(SO.sub.2CF.sub.2CHF.sub.2);

Li(SO.sub.2F)N(SO.sub.2CF.sub.2CH.sub.2F); Li(SO.sub.2CF.sub.3)N(SO.sub.2CH.sub.3);

Li(SO.sub.2CF.sub.3)N(SO.sub.2CHF.sub.2); Li(SO.sub.2CF.sub.3)N(SO.sub.2CH.sub.2F);

Li(SO.sub.2CF.sub.3)N(SO.sub.2CH.sub.2CF.sub.3), or a mixture of any two or more thereof.

13. The electrochemical cell of claim 1, wherein the lithium fluorinated sulfonylimide salt comprises LiN(SO.sub.2F).sub.2.

14. The electrochemical cell of claim 1, wherein the electrolyte comprises greater than 50 wt % of the terminally fluorinated glycol ether.

15. The electrochemical cell of claim 1, wherein the cathode comprises a metal oxide selected from a lithium nickel manganese cobalt oxide (NMC), a lithium cobalt oxide (LCO), and a lithium iron phosphate oxide (LFP).

16. The electrochemical cell of claim 1, wherein a ratio terminally fluorinated glycol ether to ionic liquid is from about 6 to 1 to about 2:1.

17. The electrochemical cell of claim 1, wherein a ratio terminally fluorinated glycol ether to ionic liquid is about 4 to 1.

18. The electrochemical cell of claim 1, wherein the separator comprising a polyolefin.

19. The electrochemical cell of claim 18, wherein the polyolefin is an aluminum oxide-filled polyolefin.

20. The electrochemical cell of claim 19, wherein the polyolefin is an aluminum oxide-filled polypropylene.

21. The electrochemical cell of claim 1, wherein the terminally fluorinated glycol ether is 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and the ionic liquid comprises a salt of N-methyl-N-propylpyrrolidinium.

22. The electrochemical cell of claim 1, wherein the terminally fluorinated glycol ether is 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and the ionic liquid comprises N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide.

23. An electrochemical cell comprising: a cathode comprising oxygen or a metal oxide; an anode comprising lithium metal; a separator comprising an aluminum oxide-filled polypropylene; and an

electrolyte comprising: $\text{LiN}(\text{SO}_2\text{F})_2$; 1,1,2,2-tetrafluoroethyl 2,2,3,3-tetrafluoropropyl ether, 1,1,1-trifluoro-2-(2-(2-(2,2,2-trifluoroethoxy)ethoxy)ethoxy)ethane, or a mixture thereof; and N-methyl-N-propylpyrrolidinium bis(fluorosulfonyl)imide, N-methyl-N-butylpyrrolidinium bis(fluorosulfonyl)imide, 1-ethyl-3-methylimidazolium bis(fluorosulfonyl)imide, 1-methoxyethyl-3-methylpyrrolidinium bis(fluorosulfonyl)imide, or a mixture of any two or more thereof.
