

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12400792
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Jeong; Hye Yun et al.

Multilayer electronic component

Abstract

A multilayer electronic component includes a body including a dielectric layer and internal electrodes, and including first and second surfaces, third and fourth surfaces, fifth and sixth surfaces, external electrodes disposed on the third and fourth surfaces, and side margin portions disposed on the fifth and sixth surfaces. The side margin portions include a first region adjacent to the internal electrodes and a second region adjacent to outside of the side margin portions. In a Raman spectra obtained by analyzing one point located in the first and second region respectively, peak X appears in a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1 . When a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first region is $\lambda(\text{cm.sup.-1})$, a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda+0.75\text{ cm.sup.-1}$ or greater.

Inventors: Jeong; Hye Yun (Suwon-si, KR), Jung; Dong Jun (Suwon-si, KR), Chae; Hyun Sik (Suwon-si, KR), Park; Ji Eun (Suwon-si, KR), Kang; Sim Chung (Suwon-si, KR), Shim; Dae Jin (Suwon-si, KR), Lee; Eun Jung (Suwon-si, KR)

Applicant: SAMSUNG ELECTRO-MECHANICS CO., LTD. (Suwon-si, KR)

Family ID: 1000008780722

Assignee: SAMSUNG ELECTRO-MECHANICS CO., LTD. (Suwon-si, KR)

Appl. No.: 18/387139

Filed: November 06, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240249882 A1	Jul. 25, 2024

Foreign Application Priority Data

KR	10-2023-0008871	Jan. 20, 2023
----	-----------------	---------------

Publication Classification

Int. Cl.: H01G4/12 (20060101); H01G4/012 (20060101); H01G4/30 (20060101)

U.S. Cl.:

CPC H01G4/1227 (20130101); H01G4/012 (20130101); H01G4/30 (20130101);

Field of Classification Search

CPC: H01G (4/1227); H01G (4/012); H01G (4/30); H01G (4/32)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2010/0181200	12/2009	Yang	427/113	B82Y 40/00
2015/0348712	12/2014	Lee	156/89.12	H01G 4/30
2016/0196918	12/2015	Hong	361/301.4	H01G 4/232
2017/0169952	12/2016	Kato	N/A	H01G 4/2325
2018/0012702	12/2017	Azuma et al.	N/A	N/A
2018/0261390	12/2017	Sakate	N/A	H01G 4/30
2019/0189353	12/2018	Tanaka	N/A	H01G 4/30
2019/0371528	12/2018	Takashima	N/A	H01G 4/012
2020/0035416	12/2019	Kwon	N/A	H01G 4/30
2020/0126721	12/2019	Fukunaga	N/A	H01G 4/012
2020/0126724	12/2019	Takagi	N/A	N/A
2020/0373087	12/2019	Kato	N/A	N/A
2021/0202179	12/2020	Saito	N/A	H01G 4/1218
2021/0202180	12/2020	Fukunaga et al.	N/A	N/A
2022/0102076	12/2021	Isota et al.	N/A	N/A
2022/0139631	12/2021	Yoshida	N/A	N/A
2022/0216478	12/2021	Ito	N/A	H01M 4/364
2022/0223344	12/2021	Jung	N/A	H01G 4/1227
2022/0230809	12/2021	Chun et al.	N/A	N/A
2022/0367117	12/2021	Lee et al.	N/A	N/A
2023/0027057	12/2022	Yamazaki	N/A	H01G 4/085

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2019-212716	12/2018	JP	N/A

OTHER PUBLICATIONS

Search Report dated May 22, 2024 issued in corresponding European Patent Application No. 23209439.1. cited by applicant

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

(1) This application claims benefit of priority to Korean Patent Application No. 10-2023-0008871 filed on Jan. 20, 2023 in the Korean Intellectual Property Office, the disclosure of which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

(2) The present disclosure relates to a multilayer electronic component.

(3) A multilayer ceramic capacitor (MLCC), a multilayer electronic component, is a chip-type capacitor mounted on the printed circuit boards of various types of electronic products, such as image display devices including liquid crystal displays (LCDs) and plasma display panels (PDPs), computers, smartphones, cell phones, and the like, to allow electricity to be charged therein and discharged therefrom.

(4) Such an MLCC may be used as a component of various electronic devices due to advantages thereof, such as compactness, guaranteed high capacitance, and ease of mounting. As various electronic devices, such as computers and mobile devices, have been reduced in size and increased in power, demand for miniaturization and high capacitance of MLCCs have been increased.

(5) MLCCs may generally include a body in which dielectric layers and internal electrodes are alternately disposed and a side margin portion disposed on a side surface of the body to protect the body.

(6) Meanwhile, in order to achieve miniaturization and high capacitance of MLCCs, side margin portions thereof have been thinned, but as the thickness of the side margin portions decreases, moisture resistance reliability of MLCCs may deteriorate.

(7) In particular, when a method of laminating a separate dielectric sheet on the side surface of the body is applied to reduce the thickness of the side margin portion, an interface between the body and the side margin portion, in particular, an interface between a capacitance forming portion in which dielectric layers and internal electrodes are alternately arranged to form capacitance and the side margin portion may be separated due to a difference in internal stress, and external moisture or hydrogen may penetrate into the interface, thereby deteriorating reliability of MLCCs.

(8) Therefore, there is a need for research to improve the moisture resistance reliability of MLCCs by minimizing residual stress mismatch at the interface between the body and the side margin portion by controlling the internal stress of the side margin portion.

SUMMARY

(9) An aspect of the present disclosure is to provide a multilayer electronic component having moisture resistance reliability, while a side margin portion thereof is thinned.

(10) However, the object of the present disclosure is not limited to the above, and will be more easily understood in the course of describing specific exemplary embodiments in the present disclosure.

(11) According to an aspect of the present disclosure, a multilayer electronic component includes a body including a dielectric layer and first and second internal electrodes alternately disposed in a first direction with the dielectric layer interposed therebetween and including first and second surfaces facing each other in the first direction, third and fourth surfaces connected to the first and second surfaces and facing each other in a second direction, and fifth and sixth surfaces connected to the first to fourth surfaces and facing each other in a third direction, an external electrode disposed on the third and fourth surfaces, and a side margin portion disposed on the fifth and sixth surfaces, wherein the side margin portion includes a first region adjacent to the internal electrodes

and a second region adjacent to outside of the side margin portions, and in a Raman spectra obtained by analyzing at least one point located in the first region and at least one point located in the second region in a central region in the first direction in a cross-section in the first and third directions of the side margin portions through Raman spectroscopy, peak X appears in a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1, and when a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first region is λ (cm.sup.-1), a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda+0.75$ cm.sup.-1 or greater.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) The above and other aspects, features, and advantages of the present disclosure will be more clearly understood from the following detailed description, taken in conjunction with the accompanying drawings, in which:
- (2) FIG. 1 is a perspective view schematically illustrating a multilayer electronic component according to an exemplary embodiment in the present disclosure;
- (3) FIG. 2 is an exploded perspective view schematically illustrating a body and side margin portions illustrated in FIG. 1;
- (4) FIG. 3 is a cross-sectional view taken along line I-I' illustrated in FIG. 1;
- (5) FIG. 4 is a cross-sectional view taken along line II-II' illustrated in FIG. 1;
- (6) FIG. 5 is an enlarged view of region K1 illustrated in FIG. 4;
- (7) FIG. 6 is a diagram schematically illustrating a Raman spectrum of a BaTiO.sub.3-based material;
- (8) FIG. 7 is a diagram illustrating a relationship between peaks appearing in the Raman spectrum of a BaTiO.sub.3-based material and compressive strain; and
- (9) FIG. 8 is a diagram illustrating a Raman shift in which a peak X appears in Raman spectra obtained by analyzing a plurality of points located in a first region and a second region through Raman spectroscopy.

DETAILED DESCRIPTION

- (10) Hereinafter, exemplary embodiments of the present inventive concept will be described in detail with reference to the accompanying drawings. The inventive concept may, however, be exemplified in many different forms and should not be construed as being limited to the specific exemplary embodiments set forth herein. Rather, these exemplary embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the inventive concept to those skilled in the art. In the drawings, the shapes and dimensions of elements may be exaggerated for clarity, and the same reference numerals will be used throughout to designate the same or like elements.
- (11) To clarify the present disclosure, portions irrespective of description are omitted and like numbers refer to like elements throughout the specification, and in the drawings, the thickness of layers, films, panels, regions, etc., are exaggerated for clarity. Also, in the drawings, like reference numerals refer to like elements although they are illustrated in different drawings. Throughout the specification, unless explicitly described to the contrary, the word "comprise" and variations, such as "comprises" or "comprising," will be understood to imply the inclusion of stated elements but not the exclusion of any other elements.
- (12) In the drawing, a first direction may be defined as a thickness (T) direction, a second direction may be defined as a length (L) direction, and a third direction may be defined as a width (W) direction.
- (13) Multilayer Electronic Component

- (14) FIG. 1 is a perspective view schematically illustrating a multilayer electronic component according to an exemplary embodiment in the present disclosure.
- (15) FIG. 2 is an exploded perspective view schematically illustrating a body and side margin portions of FIG. 1.
- (16) FIG. 3 is a cross-sectional view taken along line I-I' of FIG. 1.
- (17) FIG. 4 is a cross-sectional view taken along line II-II' of FIG. 1.
- (18) FIG. 5 is an enlarged view of region K1 of FIG. 4.
- (19) FIG. 6 is a diagram schematically illustrating a Raman spectrum of a BaTiO₃-based material.
- (20) FIG. 7 is a diagram illustrating a relationship between peaks appearing in the Raman spectrum of a BaTiO₃-based material and compressive strain.
- (21) FIG. 8 is a diagram illustrating a Raman shift in which a peak X appears in Raman spectra obtained by analyzing a plurality of points located in a first region and a second region through Raman spectroscopy.
- (22) Hereinafter, a multilayer electronic component **100** according to an exemplary embodiment in the present disclosure will be described in detail with reference to FIGS. 1 to 8. In addition, a multilayer ceramic capacitor (MLCC) will be described as an example of the multilayer electronic component, but the present disclosure is not limited thereto and may be applied to various multilayer electronic components, such as inductors, piezoelectric devices, varistors, or thermistors.
- (23) The multilayer electronic component **100** according to an exemplary embodiment in the present disclosure may include a body **110** including a dielectric layer **111** and first and second internal electrodes **121** and **122** alternately disposed in the first direction with the dielectric layer **111** interposed therebetween and including first and second surfaces **1** and **2** facing each other in the first direction, third and fourth surfaces **3** and **4** connected to the first and second surfaces and facing each other in the second direction, and fifth and sixth surfaces **5** and **6** connected to the first to fourth surfaces and facing each other in the third direction; external electrodes **131** and **132** disposed on the third and fourth surfaces; and side margin portions **141** and **142** disposed on the fifth and sixth surfaces, wherein the side margin portions **141** and **142** may include first regions **141a** and **142a** adjacent to the internal electrodes and second regions **141b** and **142b** adjacent to outside of the side margin portions, and in the Raman spectra obtained by analyzing at least one point located in the first regions **141a** and **142a** and at least one point located in the second regions **141b** and **142b** in a central region in the first direction of cross-sections in the first and third directions of the side margin portions **141** and **142** through Raman spectroscopy, peak X appears in a Raman shift of 450 cm^{sup.}-1 to 600 cm^{sup.}-1, and when a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first regions **141a** and **142a** is λ (cm^{sup.}-1), a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** may be $\lambda+0.75$ cm^{sup.}-1 or greater.
- (24) As described above, due to the structure in which the dielectric layer **111** and the internal electrodes **121** and **122** are alternately stacked, a relatively high tensile strain may occur in the body **110**, compared to the side margin portions **141** and **142**. As a result, a phenomenon in which an interface between the body **110** and the side margin portions **141** and **142** is parted may occur due to a stress mismatch between the body **110** and the side margin portions **141** and **142** and reliability of the multilayer electronic component **100** may deteriorate as external moisture and/or hydrogen penetrates through the interface between the body **110** and the side margin portions **141** and **142**.
- (25) Meanwhile, in the side margin portions **141** and **142** according to an exemplary embodiment in the present disclosure, the first regions **141a** and **142a** adjacent to the body **110** have tensile stress higher than the second regions **141b** and **142b**, stress mismatch between the body **110** and the side margin portions **141** and **142** may be minimized, thereby preventing a phenomenon in which the interface between the body **110** and the side margin portions **141** and **142** is opened.

(26) Meanwhile, as the tensile stress remaining in the side margin portions **141** and **142** is higher, cracks may more easily occur due to external impact, but in the side margin portions **141** and **142** according to an exemplary embodiment in the present disclosure, since the second regions **141b** and **142b** adjacent to the outside of the side margin portions have a compressive strain compared to the first regions **141a** and **142a**, cracks caused by external impact may be prevented, thereby improving reliability of the multilayer electronic component **100**.

(27) Hereinafter, each component included in the multilayer electronic component **100** according to an exemplary embodiment in the present disclosure will be described in more detail.

(28) Although a specific shape of the body **110** is not particularly limited, as shown, the body **110** may have a hexahedral shape or a shape similar thereto. Due to the shrinkage of ceramic powder included in the body **110** or polishing of corners during a sintering process, the body **110** may not have a perfectly straight hexahedral shape but may have a substantially hexahedral shape.

(29) The body **110** may include the first and second surfaces **1** and **2** facing each other in the first direction, the third and fourth surfaces **3** and **4** connected to the first and second surfaces **1** and **2** and facing each other in the second direction, and the fifth and sixth surfaces **5** and **6** connected to the first to fourth surfaces **1**, **2**, **3**, and **4** and facing each other in the third direction.

(30) In the body **110**, the dielectric layers **111** and the internal electrodes **121** and **122** may be alternately stacked. The plurality of dielectric layers **111** constituting the body **110** are in a sintered state, and adjacent dielectric layers **111** may be integrated such that boundaries therebetween may not be readily apparent without using a scanning electron microscope (SEM).

(31) The dielectric layer **111** may be formed by preparing a ceramic slurry including ceramic powder, an organic solvent, and a binder, applying and drying the slurry on a carrier film to prepare a ceramic green sheet, and then firing the ceramic green sheet. The ceramic powder is not particularly limited as long as sufficient capacitance may be obtained, but for example, a barium titanate-based material, a lead composite perovskite-based material, or a strontium titanate-based material may be used. Examples of the ceramic powder include $\text{BaTiO}_{3.3}$ and $(\text{Ba}_{1-x}\text{Ca}_x)\text{TiO}_{3.3}$ ($0 < x < 1$), $\text{Ba}(\text{Ti}_{1-y}\text{Ca}_y)\text{O}_{3.3}$ ($0 < y < 1$), $(\text{Ba}_{1-x}\text{Ca}_x)(\text{Ti}_{1-y}\text{Zr}_y)\text{O}_{3.3}$ ($0 < x < 1$, $0 < y < 1$) or $\text{Ba}(\text{Ti}_{1-y}\text{Zr}_y)\text{O}_{3.3}$ ($0 < y < 1$) in which Ca, Zr, etc. is partially dissolved in $\text{BaTiO}_{3.3}$.

(32) The internal electrodes **121** and **122** may be alternately disposed with the dielectric layer **111**. For example, the first internal electrode **121** and the second internal electrode **122**, which are a pair of electrodes having different polarities, may be alternately disposed in the first direction with the dielectric layer **111** interposed therebetween. The first internal electrode **121** and the second internal electrode **122** may be electrically separated from each other by the dielectric layer **111** disposed therebetween.

(33) The first internal electrode **121** may be disposed to be connected to the third, fifth, and sixth surfaces **3**, **5**, and **6** and spaced apart from the fourth surface **4**. In addition, the second internal electrode **122** may be disposed to be connected to the fourth, fifth, and sixth surfaces **4**, **5**, and **6** and spaced apart from the third surface **3**.

(34) Conductive metals included in the internal electrodes **121** and **122** may include one or more of nickel (Ni), copper (Cu), palladium (Pd), silver (Ag), gold (Au), platinum (Pt), tin (Sn), tungsten (W), titanium (Ti), and alloys thereof, but the present disclosure is not limited thereto.

(35) The internal electrodes **121** and **122** may be formed by applying a conductive paste for internal electrodes including a conductive metal to have a predetermined thickness on a ceramic green sheet and firing the conductive paste. As a method of printing the conductive paste for internal electrodes, a screen-printing method or a gravure printing method may be used, but the present disclosure is not limited thereto.

(36) The body **110** may include a capacitance forming portion **Ac** disposed inside the body **110** and forming capacitance by including the first and second internal electrodes **121** and **122** alternately disposed with the dielectric layer **111** interposed therebetween and a first cover portion **112** and a

second cover portion **113** respectively disposed on both end surfaces of the capacitance forming portion **Ac** facing each other in the first direction. The cover portions **112** and **113** may basically serve to prevent damage to the internal electrodes due to physical or chemical stress. The cover portions **112** and **113** may have the same dielectric composition as that of the dielectric layer **111** except that they do not include internal electrodes, but the present disclosure is not limited thereto, and the cover portions **112** and **113** may have a dielectric composition different from that of the dielectric layer **111**.

(37) The external electrodes **131** and **132** may be disposed on the third and fourth surfaces **3** and **4** of the body **110**, and extend onto portions of the first, second, fifth, and sixth surfaces. In addition, the external electrodes **131** and **132** may include a first external electrode **131** connected to the first internal electrode **121** and a second external electrode **132** connected to the second internal electrode **122**.

(38) The external electrodes **131** and **132** may be formed by dipping the third and fourth surfaces **3** and **4** of the body **110** in a conductive paste for external electrodes including a conductive metal and glass and then performing sintering. Alternatively, the external electrodes **131** and **132** may be formed by transferring a sheet including conductive metal and glass.

(39) The conductive metal included in the external electrodes **131** and **132** may be copper (Cu), nickel (Ni), palladium (Pd), platinum (Pt), gold (Au), silver (Ag), lead (Pb), and/or alloys thereof, but the present disclosure is not limited thereto.

(40) Also, although not shown, a first plating layer may be disposed on the first external electrode **131** and a second plating layer may be disposed on the second external electrode. The plating layers may improve mounting characteristics. The type of the plating layers is not particularly limited, and may be plating layers including nickel (Ni), tin (Sn), palladium (Pd), and/or alloys thereof, or may be formed of a plurality of layers. The plating layers may be, for example, nickel (Ni) plating layers or tin (Sn) plating layers, or may have a form in which a nickel (Ni) plating layer and a tin (Sn) plating layer are sequentially formed. In addition, the plating layers may include a plurality of nickel (Ni) plating layers and/or a plurality of tin (Sn) plating layers.

(41) In the drawings, a structure in which the multilayer electronic component **100** has two external electrodes **131** and **132** is described, but the present disclosure is not limited thereto, and the number or shape of the external electrodes **131** and **132** may be determined according to the shape of the internal electrodes **121** and **122** or other purposes.

(42) The side margin portions **141** and **142** may be disposed on the fifth and sixth surfaces **5** and **6**. The side margin portions may include a first side margin portion **141** disposed on the fifth surface and a second side margin portion **142** disposed on the sixth surface. The side margin portions **141** and **142** may basically serve to prevent damage to the internal electrodes **121** and **122** due to physical or chemical stress.

(43) The side margin portions **141** and **142** may include a BaTiO₃-based material, as a main component, and here, the BaTiO₃-based material may include BaTiO₃ and (Ba_{1-x}Ca_x)TiO₃ (0<x<1), Ba(Ti_{1-y}Ca_y)O₃ (0<y<1), (Ba_{1-x}Ca_x)(Ti_{1-y}Zr_y)O₃ (0<x<1, 0<y<1) or Ba(Ti_{1-y}Zr_y)O₃ (0<y<1) in which Ca, Zr, and the like are partially dissolved in BaTiO₃. The side margin portions **141** and **142** may include substantially the same material as that of the dielectric layer **111**, but the present disclosure is not limited thereto.

(44) Hereinafter, the first regions **141a** and **142a** and the second regions **141b** and **142b** of the side margin portions **141** and **142** will be described in more detail. Meanwhile, although FIG. 5 illustrates the first region **142a** and the second region **142b** of the second side margin portion **142**, the first side margin portion **141** and the second side margin portion **142** are symmetrical to each other in the third direction, and thus, the description with reference to FIG. 5 is regarded as including the description of the first side margin portion **141**.

(45) The side margin portions **141** and **142** may include first regions **141a** and **142a** adjacent to the

body **110** and second regions **141b** and **142b** adjacent to the outside of the side margin portion. According to an exemplary embodiment in the present disclosure, in the Raman spectra obtained by analyzing at least one point located in the first regions **141a** and **142a** and at least one point located in the second regions **141b** and **142b** in a central region in the first direction of cross-sections in the first and third directions of the side margin portions **141** and **142** through Raman spectroscopy, peak X appears in a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1. Here, the cross-sections in the first and third directions of the side margin portions **141** and **142** may be cross-sections in the first and third directions taken in the center of the side margin portions **141** and **142** in the second direction, for example.

(46) For example, referring to FIGS. **4** and **5**, in the Raman spectra obtained by analyzing at least one point P11 to P16, P21 to P26, P31 to P36, and P41 to P46 located in the first region **142a** through Raman spectroscopy, peak X may appear at a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1, and in the Raman spectra obtained by analyzing at least one point P17 to P112, P27 to P212, P37 to P312, and P47 to P412 located in the second region **142b** through Raman spectroscopy, peak X may appear at a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1.

(47) Referring to FIG. **6**, peaks may appear at Raman shifts near 250 cm.sup.-1, 360 cm.sup.-1, 514 cm.sup.-1, 716 cm.sup.-1 in the Raman spectrum of a BaTiO.sub.3-based material, and four peaks near 250 cm.sup.-1, 360 cm.sup.-1, 514 cm.sup.-1, 716 cm.sup.-1 may derived from A.sub.1(TO), B.sub.1+E (TO), A.sub.1(TO)+E(TO), A.sub.1(LO)+E (LO) vibrations. Here, the peak X appears at a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1, and refer to a peak derived from A₁ (TO)+E (TO) vibrations.

(48) According to an exemplary embodiment in the present disclosure, when the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first regions **141a** and **142a** is 2λ (cm.sup.-1), the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** may be $\lambda+0.75$ cm.sup.-1 or more.

Hereinafter, the Raman shift at which the peak X appears means a Raman shift value at which the peak X of maximum intensity appears at a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1.

(49) Here, the minimum value z of the Raman shift at which the peak X appears in the Raman spectra of the first regions **141a** and **142a** may refer to the minimum value of the Raman shift at which the peak X appears when a plurality of points P11 to P16, P21 to P26, P31 to P36, and P41 to P46 located in the first regions **141a** and **142a** in the central region in the first direction of the cross-sections in the first and third directions of the side margin portions **141** and **142** and equally spaced in the first direction and equally spaced in the third direction are analyzed by Raman spectroscopy.

(50) In addition, the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** may refer to the minimum value of the Raman shift at which the peak X appears when a plurality of points P17 to P112, P27 to P212, P37 to P312, and P47 to P412 located in the second regions **141b** and **142b** in the central region in the first direction of the cross-sections in the first and third directions of the side margin portions **141** and **142** and equally spaced in the first direction and equally spaced in the third direction are analyzed by Raman spectroscopy. The number of points located in the first region and the second region may not be particularly limited and may be appropriately selected according to the size of the side margin portion in the first direction and in the third direction.

(51) Referring to FIG. **7**, the Raman shift at which the peak X appears may vary depending on stress remaining in the BaTiO.sub.3-based material. For example, when a tensile strain relatively acts, the Raman shift value at which the peak X appears may decrease, and when a compressive strain relatively acts, the Raman shift value at which the peak X appears may increase. In particular, the peak X reacts more sensitively to the stress remaining in the BaTiO.sub.3-based material than the peaks derived from A.sub.1(TO), B.sub.1+E(TO) and A.sub.1(LO)+E(LO) vibrations. Therefore, in the present disclosure, the stress remaining in the first regions **141a** and

142a and the second regions **141b** and **142b** is evaluated based on the Raman shift value at which the peak X appears. In addition, analyzing the points located in the central region in the first direction of the cross-sections in the first and third directions of the side margin portions **141** and **142** is to evaluate the stress remaining in the central region in the first direction, which is more affected by internal stress than the outer region in the first direction of the cross-sections in the first and third directions of the side margin portions **141** and **142**.

(52) That the minimum value of the Raman shift at which the peak X appears satisfies $\lambda+0.75$ cm.sup.-1 or more in the Raman spectra of the second regions **141b** and **142b** means that the first regions **141a** and **142a** relatively have tensile stress compared to the second regions **141b** and **142b** and the second regions **141b** and **142b** relatively have compressive stress compared to the first regions **141a** and **142a**.

(53) Accordingly, the first regions **141a** and **142a** may serve to minimize mismatch with the body **110** in which the dielectric layer **111** and the internal electrodes **121** and **122** are stacked so that the tensile stress is relatively high compared to the side margin portions **141** and **142**, thereby preventing a phenomenon in which the interface between the body **110** and the side margin portions **141** and **142** is opened, thereby preventing penetration of external moisture and/or hydrogen to improve reliability of the multilayer electronic component **100**.

(54) In addition, as the tensile stress remaining in the side margin portions **141** and **142** increases, cracks may easily occur due to external impact, but, in the multilayer electronic component **100** according to an exemplary embodiment in the present disclosure, since the second regions **141b** and **142b** adjacent to the outside of the side margin portions **141** and **142** have compressive stress compared to the first regions **141a** and **142a**, cracks caused by external shocks may be prevented, thereby effectively improve the reliability of the multilayer electronic component **100**.

(55) An upper limit of the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** may not be particularly limited, but may be, for example, $\lambda\lambda+1.2$ cm.sup.-1 or less. When the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** exceeds $\lambda+1.2$ cm.sup.-1, the interface between the body **110** and the side margin portions **141** and **142** may be opened.

(56) In an exemplary embodiment, when an average value of the Raman shift at which the peak X appears in the Raman spectra of the first region **141a** and **142a** is λ_1 and an average value of the Raman shift at which the peak X appears in the Raman spectra of the second region **141b** and **142b** is λ_2 , $\lambda_2>\lambda_1$ may be satisfied. For example, λ_1 may refer to the average value of Raman shifts at which the peak X appears when the plurality of points P11 to P16, P21 to P26, P31 to P36, and P41 to P46 located in the first region are analyzed by Raman spectroscopy, and λ_2 may refer to the average value of Raman shifts at which the peak X appears when the plurality of points P17 to P112, P27 to P212, P37 to P312, and P47 to P412 located in the second region are analyzed by Raman spectroscopy. By satisfying $\lambda_2>\lambda_1$, the effect of minimizing stress mismatch and preventing cracks due to external impact may become more remarkable.

(57) A boundary between the first regions **141a** and **142a** and the second regions **141b** and **142b** may be defined as follows. For example, in two imaginary lines adjacent to each other among a plurality of imaginary lines equally spaced in the third direction from the central region in the first direction of the end surfaces of the side margin portions **141** and **142** in the first and third directions, when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points equally spaced from each other located on one imaginary line is λ_m and when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points equally spaced from each other located on the other imaginary line satisfies $\lambda_m+0.5$ cm.sup.-1 or more, the boundary between the first regions **141a** and **142a** and the second regions **141b** and **142b** may be located in the center between the two imaginary lines adjacent to each other.

(58) For example, as illustrated in FIG. 5, in the sixth and seventh imaginary lines L6 and L7 adjacent to each other among a plurality of imaginary lines equally spaced in the third direction,

when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points P16, P26, P36, and P46 equally spaced from each other located on the sixth imaginary line L6 is λ_m and when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points P17, P27, P37, and P47 equally spaced from each other located on the seventh imaginary line L7 satisfies $\lambda_m + 0.5 \text{ cm}^{-1}$ or more, the boundary between the first region and the second region may be located in the center between the sixth imaginary line L6 and the seventh imaginary line L7. Meanwhile, referring to FIGS. 5 and 8, there are a total of 12 imaginary lines, but the number of imaginary lines may vary depending on the size of the side margin portions **141** and **142** in the third direction.

(59) Referring to FIG. 5, in an exemplary embodiment, the size of the first region **142a** in the third direction measured from the central region of the side margin portion **142** in the first direction is T1 and the size of the second region **142b** in the third direction measured from the central region of the side margin portion **142** in the first direction is T2, T2/T1 may satisfy 0.6 or more and 2.2 or less. If T2/T1 is less than 0.6, the size of the second region **142b** in the third direction may be too small to prevent cracks due to external impact and improve the reliability. If T2/T1 exceeds 2.2, the size of the side margin portions **141** and **142** in the third direction may excessively increase, causing the boundary between the body **110** and the side margin portions **141** and **142** to be opened, thereby deteriorating the reliability of the multilayer electronic component.

(60) A method for adjusting the T2/T1 ratio may not be particularly limited. For example, as the size of the side margin portions **141** and **142** in the third direction increases, the T2/T1 ratio may increase. In addition, the T1 and T2 may be measured, for example, by imaging the cross-sections in the first and third directions taken in the center of the side margin portion in the second direction with a scanning electron microscope (SEM) and defining the boundary between the first regions **141a** and **142a** and the second regions **141b** and **142b** through Raman spectroscopy. Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(61) The side margin portions **141** and **142** may be formed by, for example, laminating a dielectric sheet including a dielectric material including BaTiO₃-based powder as a main component on the fifth and sixth surfaces **5** and **6** and then performing sintering thereon. The method of adjusting the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first regions **141a** and **142a** and the second regions **141b** and **142b** may not be particularly limited, but, for example, the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first regions **141a** and **142a** and the second regions **141b** and **142b** may be adjusted by sintering the dielectric sheet including a dielectric material including Sn-doped BaTiO₃-based powder and adjusting the amount of shrinkage of the side margin portions **141** and **142** during sintering. Accordingly, the side margin portions **141** and **142** may include Sn.

(62) In an exemplary embodiment, an average size of dielectric grains included in the first regions **141a** and **142a** may be greater than the average size of dielectric grains included in the second regions **141b** and **142b**, but the present disclosure is not limited thereto. The average size of the dielectric grains included in the first region and the average size of the dielectric grains included in the second region may be obtained by obtaining an image of central region (region K1 of FIG. 4, for example) in the first direction of the side margin portions **141** and **142** in the cross-sections in the first and third directions taken at the center of the multilayer electronic component in the second direction, which is magnified 50,000 times with an SEM and then analyzing the image using an image analysis program, for example, the Zotos Program by the Zotos. Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(63) The average size of the side margin portions **141** and **142** in the third direction may not be particularly limited. However, in general, as the average size of the side margin portions **141** and **142** in the third direction decreases, the reliability of the multilayer electronic component

deteriorates. Meanwhile, in the case of the multilayer electronic component according to an exemplary embodiment in the present disclosure, the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** satisfies $\lambda + 0.75 \text{ cm.sup.-1}$ or more, the reliability of the multilayer electronic component may be secured even when the average size of the side margin portions **141** and **142** in the third direction is 15 μm or less. A lower limit of the average size of the side margin portions **141** and **142** in the third direction is not particularly limited, but may be, for example, 2 μm or more.

(64) The average size of the side margin portions **141** and **142** in the third direction refers to the average thickness of each of the first side margin portion **141** and the second side margin portion **142**. In addition, the average thickness of the side margin portions **141** and **142** may be a value obtained by averaging sizes in the third direction measured from a five equally points in an image obtained by scanning the cross-sections of the side margin portions **141** and **142** in the first and third directions with an SEM. Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(65) In an exemplary embodiment, when the size of the side margin portions **141** and **142** in the third direction corresponding to the central region of the body **110** in the first direction is tm_1 and the size of the side margin portions **141** and **142** in the third direction in contact with the ends of the internal electrodes **121** and **122** arranged at the outermost portion based on the first direction is tm_2 , tm_2/tm_1 may be greater than or equal to 0.9 and less than or equal to 1.0.

(66) In the related art, since the side margin portion is formed by applying or printing a ceramic slurry, the thickness of the side margin portions varies significantly depending on positions. Specifically, in the related art, the thickness of the first or second side margin portion region corresponding to the central region of the body in the first direction is thicker than that of other regions. As described above, in the case of the related art in which the variations of the thicknesses of positions of the side margin portions are large, the portion occupied by the side margin portions is large in a multilayer electronic component of the same size, and thus, it may be difficult to secure high capacitance because the size of the capacitance forming portion cannot be secured.

(67) Meanwhile, according to an exemplary embodiment in the present disclosure, because tm_2/tm_1 satisfies 0.9 or more and 1.0 or less, the size of the first and second side margin portions **M1** and **M2** in the third direction may be formed to be small, thereby forming the capacitance portion **Ac**.

(68) In addition, the tm_2 and tm_1 may be measured, for example, by imaging the cross-sections in the first and third directions taken in the center of the side margin portion in the second direction with a scanning electron microscope (SEM). Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(69) In addition, when the thickness of the side margin portions **141** and **142** in contact with the edge of the body **110** is tm_3 , tm_3/tm_1 may be 0.9 or more and 1.0 or less. Due to the above characteristics, the variations in thickness of each region of the side margin portions may be reduced and the size of the capacitance forming portion **Ac** may be secured to be large, thereby implementing the multilayer electronic component having high capacitance.

(70) The average thickness td of the dielectric layer **111** may not be particularly limited. However, as the thickness of the dielectric layer **111** decreases, cracks may easily occur in the body **110** due to stress generated when a voltage is applied, and accordingly, the reliability of the multilayer electronic component may deteriorate. Meanwhile, in the case of the multilayer electronic component according to an exemplary embodiment in the present disclosure, since the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** satisfies $\lambda + 0.75 \text{ cm.sup.-1}$ or more, the reliability of the multilayer electronic component may be secured, even when the average thickness td of at least one of the dielectric layers **111** is 0.4 μm or less.

(71) Here, the average thickness td of the dielectric layer **111** refers to the size of the dielectric

layer **111** disposed between the internal electrodes **121** and **122** in the first direction. The average thickness of the dielectric layer **111** may be measured by scanning cross-sections of the body **110** in the first and second directions with an SEM at a magnification of 10,000. More specifically, the average value may be measured by measuring the thicknesses at a plurality of points of one dielectric layer **111**, for example, at 30 points equally spaced in the second direction. The 30 equally spaced points may be designated in the capacitance forming portion **Ac**. In addition, if the average value is measured by extending the average value measurement to ten dielectric layers **111**, the average thickness of the dielectric layers **111** may be further generalized. Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(72) The average thickness t_e of the internal electrodes **121** and **122** may not be particularly limited. However, in the case of the multilayer electronic component according to an exemplary embodiment in the present disclosure, since the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** satisfies $\lambda + 0.75 \text{ cm} \cdot \text{sup.} - 1$ or more, the reliability of the multilayer electronic component may be secured even when the average thickness of at least one of the first internal electrodes **121** is $0.4 \mu\text{m}$ or less and the average thickness of at least one of the second internal electrodes **122** is $0.4 \mu\text{m}$ or less.

(73) The average thickness t_e of the internal electrodes **121** and **122** refers to a size of the internal electrodes **121** and **122** in the first direction. Here, the average thickness of the internal electrodes **121** and **122** may be measured by scanning cross-sections of the body **110** in the first and second directions with a scanning electron microscope (SEM) at a magnification of 10,000. More specifically, the average value may be obtained by measuring the thickness at a plurality of points of one internal electrode **121** or **122**, for example, at 30 points equally spaced in the second direction. The 30 equally spaced points may be designated in the capacitance forming portion **Ac** to be described later. The 30 equally spaced points may be designated in the capacitance forming portion **Ac**. In addition, if the average value is measured by extending the average value measurement to ten internal electrodes **121** and **122**, the average thickness of the internal electrodes **121** and **122** may be further generalized. Other methods and/or tools appreciated by one of ordinary skill in the art, even if not described in the present disclosure, may also be used.

(74) The average thickness t_c of the cover portions **112** and **113** may not be particularly limited. However, the average thickness t_c of the cover portions **112** and **113** may be $20 \mu\text{m}$ or less in order to reduce the size and increase the capacitance of the multilayer electronic component. As described above, even when the average thickness t_c of the cover portions **112** and **113** is $20 \mu\text{m}$ or less, the reliability of the multilayer electronic component may be secured because the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second regions **141b** and **142b** satisfies $\lambda + 0.75 \text{ cm} \cdot \text{sup.} - 1$ or more. Here, the average thickness of the cover portions **112** and **113** refers to the average thickness of each of the first cover portion **112** and the second cover portion **113**.

(75) The average thickness of the cover portions **112** and **113** may refer to the average size of the cover portions **112** and **113** in the first direction, and may be a value obtained by averaging sizes in the first direction measured at five equally spaced points in the cross-sections of the body **110** in the first and second directions.

Experimental Example

(76) <Raman Shift Measurement of First Region and Second Region>

(77) First, after a body including a dielectric layer and internal electrodes was prepared, a dielectric sheet including a dielectric material including Sn-coated BaTiO₃-based powder, additives, solvents, dispersants, etc. was laminated on the fifth and sixth surfaces of the body and then sintered to form a side margin portion. After sintering, the third and fourth surfaces of the body were dipped into a conductive paste for external electrodes including Cu and then sintered to form external electrodes, thereby preparing a sample chip.

(78) Next, a central region in the first direction of the cross-sections in the first and third directions taken at the center of the side margin portion in the second direction was analyzed through Raman spectroscopy. Raman spectroscopy was used for measurement using Raman Spectroscopy (LabRam HR Evolution) equipment, and was performed under conditions of laser wavelength: 532 nm, ND filter: 3.2%, and acquisition time: 15 s.

(79) Referring to FIG. 5, first, first to twelfth imaginary lines are drawn in the third direction at a distance of about 1 μm from each other in the central region in the first direction of the cross-sections in the first and third directions of the side margin portion, and four points located about 5 μm apart from each other located on each imaginary line were analyzed by Raman spectroscopy. Here, the first imaginary line is an imaginary line closest to the body, and the twelfth imaginary line is an imaginary line closest to the outside of the side margin portion.

(80) Thereafter, in the Raman spectra obtained by analyzing four points located on each imaginary line through Raman spectroscopy, a Raman shift value at which the peak X of maximum intensity appears was obtained at a Raman shift of 450 $\text{cm}.\text{sup}.-1$ to 600 $\text{cm}.\text{sup}.-1$, and then the minimum value, maximum value, and average value of the Raman shift at which the peak X appears in the Raman spectra of four points were measured. For example, the minimum value, maximum value, and average value of the Raman shift at which the peak X appears in the Raman spectra of the four points P11 to P41 located on the first imaginary line L1 were measured, and the minimum value, maximum value, and average value of the Raman shift at which the peak X appears in the Raman spectra of the four points P12 to P42 located on the second imaginary line L2 were measured, and thereafter, Raman shift measurement was performed on the third to twelfth imaginary lines L3 to L12 in the same manner and illustrated in FIG. 8.

(81) Referring to FIGS. 5 and 8, it was confirmed that, when the average value of the Raman shifts at which the peak X appears in the Raman spectra of the four points P16 to P46 located on the sixth imaginary line L6 is λm , the average value of the Raman shift at which the peak X appears in the Raman spectra of four points P17 to P47 located on the seventh imaginary line L7 satisfies $\lambda\text{m}+0.5 \text{ cm}.\text{sup}.-1$ or more, and accordingly, the boundary between the first and second regions is defined as the center between the sixth and seventh imaginary lines L6 and L7 adjacent to each other.

(82) In addition, it was confirmed that, when the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first region is 2, the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda+0.75 \text{ cm}.\text{sup}.-1$ or more.

(83) <Evaluation of Moisture Resistance Reliability Based on T2/T1 Ratio>

(84) Thereafter, moisture resistance reliability was evaluated according to the ratio of the size T2 of the second region in the third direction to the size T1 of the first region in the third direction based on the set boundary between the first region and the second region. Moisture resistance reliability evaluation was performed by mounting 1200 chips per sample chip and applying a voltage of 10 V for 24 hours at a temperature of 85° C. and a relative humidity of 85%, and thereafter, the number of samples having insulation resistance dropped by 1 order or more than from an initial value was listed in Table 1. At this time, among the 1200 sample chips, a case in which the number of samples having insulation resistance dropped by 1 order or more from the initial value was less than 10 was judged as good (○) and a case in which the number of samples having insulation resistance dropped by 1 order or more from the initial value was 10 or more was judged as bad (X)

(85) TABLE-US-00001 TABLE 1 Test T2/ Moisture resistance No. T1 reliability test Evaluation 1 0 19/1200 X 2 0.5 15/1200 X 3 0.6 3/1200 ○ 4 0.71 1/1200 ○ 5 1 0/1200 ○ 6 2.2 2/1200 ○ 7 2.5 Test is not possible X

(86) Referring to Table 1, it can be seen that test Nos. 3 to 6, in which the T2/T1 ratio satisfies 0.6 to 2.2, have less than 10 defective samples in the moisture resistance reliability test, and the moisture resistance reliability is improved. Meanwhile, in Test Nos. 1 and 2, it can be seen that the T2/T1 ratio is less than 0.6 and the number of defective samples in the moisture resistance

reliability test is 10 or more. This is expected because the size of the second region in the third direction is too small to prevent cracks due to external impact, resulting in reduced reliability. Meanwhile, the test No. 1 in which the T2/T1 ratio is 0 means that the second region defined in the present disclosure was not formed.

(87) In addition, in the case of Test No. 7, the T2/T1 ratio exceeds 2.2, and the interface between the body and the side margin portion was opened, so the moisture resistance reliability test could not be performed.

(88) As one of the various effects of the present disclosure, it is possible to secure moisture resistance reliability of the multilayer electronic component, while the thickness of the side margin portion is reduced.

(89) While example exemplary embodiments have been illustrated and described above, it will be apparent to those skilled in the art that modifications and variations could be made without departing from the scope of the present disclosure as defined by the appended claims.

Claims

1. A multilayer electronic component comprising: a body including a dielectric layer and first and second internal electrodes alternately disposed in a first direction with the dielectric layer interposed therebetween and including first and second surfaces facing each other in the first direction, third and fourth surfaces connected to the first and second surfaces and facing each other in a second direction, and fifth and sixth surfaces connected to the first to fourth surfaces and facing each other in a third direction; an external electrode disposed on the third and fourth surfaces; and a side margin portion disposed on the fifth and sixth surfaces, wherein the side margin portion includes a first region adjacent to the internal electrodes and a second region adjacent to outside of the side margin portion, and in a Raman spectra obtained by analyzing at least one point located in the first region and at least one point located in the second region in a central region in the first direction in a cross-section in the first and third directions of the side margin portion through Raman spectroscopy, peak X appears in a Raman shift of 450 cm.sup.-1 to 600 cm.sup.-1 , and when a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the first region is $\lambda\text{ (cm.sup.-1)}$, a minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda+0.75\text{ cm.sup.-1}$ or greater.
2. The multilayer electronic component according to claim 1, wherein the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda+0.75\text{ cm.sup.-1}$ or greater and $\lambda+1.2\text{ cm.sup.-1}$ or less.
3. The multilayer electronic component according to claim 1, wherein $\lambda_2>\lambda_1$, in which λ_1 is an average value of the Raman shifts at which the peak X appears in the Raman spectra of the first region and λ_2 is an average value of the Raman shifts at which the peak X appears in the Raman spectra of the second region.
4. The multilayer electronic component according to claim 1, wherein, in two imaginary lines adjacent to each other among a plurality of imaginary lines equally spaced in the third direction from the central region in the first direction of the end surfaces of the side margin portion in the first and third directions, when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points equally spaced from each other located on one imaginary line is λ_m and when an average value of the Raman shift at which the peak X appears in the Raman spectra of four points equally spaced from each other located on the other imaginary line satisfies $\lambda_m+0.5\text{ cm.sup.-1}$ or more, the boundary between the first region and the second region is located in a center between the two imaginary lines adjacent to each other.
5. The multilayer electronic component according to claim 1, wherein the cross-section of the side margin portion in the first and third directions is a cross-section taken in a center of the side margin portion in the second direction.

6. The multilayer electronic component according to claim 1, wherein, when a size of the first region in the third direction measured in the central region of the side margin portion in the first direction is T1 and a size of the second region in the third direction measured in the central region of the side margin portion in the first direction is T2, T2/T1 satisfies 0.6 or more and 2.2 or less.
 7. The multilayer electronic component according to claim 1, wherein the side margin portion includes a BaTiO₃-based material as a main component.
 8. The multilayer electronic component according to claim 1, wherein the side margin portion includes Sn.
 9. The multilayer electronic component according to claim 1, wherein an average size of the side margin portion in the third direction is 15 μm or less.
 10. The multilayer electronic component according to claim 1, wherein an average thickness of the dielectric layer is 0.4 μm or less.
 11. The multilayer electronic component according to claim 1, wherein an average thickness of the first internal electrodes is 0.4 μm or less, and an average thickness of the second internal electrodes is 0.4 μm or less.
 12. The multilayer electronic component according to claim 1, wherein, when a size of the side margin portion region in the third direction corresponding to the central region of the body in the first direction is tm1 and a size of the side margin portion region in the third direction contacting an end of the internal electrode disposed at an outermost portion based on the first direction is tm2, tm2/tm1 is 0.9 or more and 1.0 or less.
 13. The multilayer electronic component according to claim 1, wherein, when a size of the side margin portion region in the third direction corresponding to the central region of the body in the first direction is tm1 and a thickness of the side margin portion region contacting an edge of the body is tm3, tm3/tm1 is 0.9 or more and 1.0 or less.
 14. The multilayer electronic component according to claim 1, wherein the first internal electrode is connected to the third, fifth and sixth surfaces, and the second internal electrode is connected to the fourth, fifth and sixth surfaces.
 15. The multilayer electronic component according to claim 1, wherein the side margin portion includes Sn-doped BaTiO₃-based powder.
 16. The multilayer electronic component according to claim 15, wherein, when a size of the first region in the third direction measured in the central region of the side margin portion in the first direction is T1 and a size of the second region in the third direction measured in the central region of the side margin portion in the first direction is T2, T2/T1 satisfies 0.6 or more and 2.2 or less.
 17. The multilayer electronic component according to claim 16, wherein the minimum value of the Raman shift at which the peak X appears in the Raman spectra of the second region is $\lambda + 0.75$ cm.sup.-1 or greater and $\lambda + 1.2$ cm.sup.-1 or less.
 18. The multilayer electronic component according to claim 17, wherein $\lambda_2 > \lambda_1$, in which λ_1 is an average value of the Raman shifts at which the peak X appears in the Raman spectra of the first region and λ_2 is an average value of the Raman shifts at which the peak X appears in the Raman spectra of the second region.
-