

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12400857
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Tran; Luan C. et al.

Methods of forming electronic devices using pitch reduction

Abstract

Embodiments of a method for device fabrication by reverse pitch reduction flow include forming a first pattern of features above a substrate and forming a second pattern of pitch-multiplied spacers subsequent to forming the first pattern of features. In embodiments of the invention the first pattern of features may be formed by photolithography and the second pattern of pitch-multiplied spacers may be formed by pitch multiplication. Other methods for device fabrication are provided.

Inventors: Tran; Luan C. (Meridian, ID), Giridhar; Raghupathy (San Jose, CA)

Applicant: Micron Technology, Inc. (Boise, ID)

Family ID: 1000008780625

Appl. No.: 17/662160

Filed: May 05, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220262626 A1	Aug. 18, 2022

Related U.S. Application Data

continuation parent-doc US 16692440 20191122 US 11348788 child-doc US 17662160
continuation parent-doc US 16249369 20190116 US 10522348 20191231 child-doc US 16692440
division parent-doc US 14635023 20150302 ABANDONED child-doc US 16249369
division parent-doc US 11830449 20070730 US 8980756 20150317 child-doc US 14635023

Publication Classification

Int. Cl.: H01L21/027 (20060101); H01L21/033 (20060101); H01L21/311 (20060101);
H01L21/3213 (20060101); H10B69/00 (20230101)

U.S. Cl.:

CPC H01L21/0274 (20130101); H01L21/0332 (20130101); H01L21/0337 (20130101);
H01L21/0338 (20130101); H01L21/31111 (20130101); H01L21/31133 (20130101);
H01L21/32139 (20130101); H10B69/00 (20230201);

Field of Classification Search

CPC: H01L (21/0274); H01L (21/0332); H01L (21/0337); H01L (21/0338); H01L (21/31111);
H01L (21/31133); H01L (21/32139); H10B (69/00)

USPC: 257/618

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
4091406	12/1977	Lewis	N/A	N/A
5047117	12/1990	Roberts	N/A	N/A
5254218	12/1992	Roberts et al.	N/A	N/A
5328810	12/1993	Lowrey et al.	N/A	N/A
5411909	12/1994	Manning et al.	N/A	N/A
5488011	12/1995	Figura et al.	N/A	N/A
5573837	12/1995	Roberts et al.	N/A	N/A
5618383	12/1996	Randall	N/A	N/A
5686357	12/1996	Howard	N/A	N/A
5691547	12/1996	Manning et al.	N/A	N/A
5770479	12/1997	Brooks et al.	N/A	N/A
5835225	12/1997	Thakur	N/A	N/A
5844254	12/1997	Manning et al.	N/A	N/A
5851916	12/1997	Howard	N/A	N/A
5866453	12/1998	Prall et al.	N/A	N/A
5869843	12/1998	Harshfield	N/A	N/A
5897372	12/1998	Howard	N/A	N/A
5980349	12/1998	Hofmann et al.	N/A	N/A
6049093	12/1999	Manning et al.	N/A	N/A
6077729	12/1999	Harshfield	N/A	N/A
6100180	12/1999	Howard	N/A	N/A
6117767	12/1999	Howard	N/A	N/A
6121665	12/1999	Gonzalez et al.	N/A	N/A
6124164	12/1999	Al-Shareef et al.	N/A	N/A
6271067	12/2000	Gonzalez et al.	N/A	N/A
6274423	12/2000	Prall et al.	N/A	N/A
6294824	12/2000	Brooks et al.	N/A	N/A
6297129	12/2000	Tran et al.	N/A	N/A
6307238	12/2000	Gonzalez et al.	N/A	N/A
6326652	12/2000	Rhodes	N/A	N/A

6328620	12/2000	Hu	N/A	N/A
6329750	12/2000	Hofmann et al.	N/A	N/A
6348411	12/2001	Ireland et al.	N/A	N/A
6351005	12/2001	Al-Shareef et al.	N/A	N/A
6387600	12/2001	Hanson	N/A	N/A
6410453	12/2001	Sandhu	N/A	N/A
6420250	12/2001	Cho et al.	N/A	N/A
6420259	12/2001	Howard	N/A	N/A
6422906	12/2001	Hofmann et al.	N/A	N/A
6455439	12/2001	Sandhu	N/A	N/A
6465865	12/2001	Gonzalez	N/A	N/A
6475921	12/2001	Sandhu	N/A	N/A
6492212	12/2001	Ieong et al.	N/A	N/A
6495434	12/2001	Rhodes	N/A	N/A
6501114	12/2001	Cho et al.	N/A	N/A
6515350	12/2002	Moore	N/A	N/A
6545406	12/2002	Hofmann et al.	N/A	N/A
6554671	12/2002	Hofmann et al.	N/A	N/A
6573030	12/2002	Fairbairn et al.	N/A	N/A
6607944	12/2002	Tran et al.	N/A	N/A
6624024	12/2002	Prall et al.	N/A	N/A
6624085	12/2002	Sandhu	N/A	N/A
6638441	12/2002	Chang et al.	N/A	N/A
6656371	12/2002	Drewes	N/A	N/A
6716080	12/2003	Hoffman et al.	N/A	N/A
6717351	12/2003	Hu	N/A	N/A
6734502	12/2003	Gonzalez et al.	N/A	N/A
6734619	12/2003	Hofmann et al.	N/A	N/A
6740916	12/2003	Ireland et al.	N/A	N/A
6746907	12/2003	Gonzalez et al.	N/A	N/A
6767811	12/2003	Rhodes	N/A	N/A
6770927	12/2003	Cho et al.	N/A	N/A
6806175	12/2003	Moore	N/A	N/A
6823693	12/2003	Hofmann et al.	N/A	N/A
6844580	12/2004	Rhodes	N/A	N/A
6933207	12/2004	Tran et al.	N/A	N/A
6955961	12/2004	Chung	N/A	N/A
6958519	12/2004	Gonzalez et al.	N/A	N/A
6981904	12/2005	Hofmann et al.	N/A	N/A
7037771	12/2005	Rhodes	N/A	N/A
7045834	12/2005	Tran et al.	N/A	N/A
7071067	12/2005	Ahmad	N/A	N/A
7074717	12/2005	Rhodes	N/A	N/A
7115506	12/2005	Ireland et al.	N/A	N/A
7115525	12/2005	Abatchev et al.	N/A	N/A
7151040	12/2005	Tran et al.	N/A	N/A
7153753	12/2005	Forbes	N/A	N/A
7202171	12/2006	Trapp	N/A	N/A
7253118	12/2006	Tran et al.	N/A	N/A
7262428	12/2006	Forbes	N/A	N/A

7268054	12/2006	Tran et al.	N/A	N/A
7341906	12/2007	Hwang et al.	N/A	N/A
7361569	12/2007	Tran et al.	N/A	N/A
7368362	12/2007	Tran et al.	N/A	N/A
7368790	12/2007	Forbes	N/A	N/A
7390746	12/2007	Bai et al.	N/A	N/A
7393789	12/2007	Abatchev et al.	N/A	N/A
7396781	12/2007	Wells	N/A	N/A
7429536	12/2007	Abatchev et al.	N/A	N/A
7435536	12/2007	Sandhu et al.	N/A	N/A
7455956	12/2007	Sandhu et al.	N/A	N/A
7473644	12/2008	Lane et al.	N/A	N/A
7473647	12/2008	Lee et al.	N/A	N/A
7488685	12/2008	Kewley	N/A	N/A
7517764	12/2008	Booth et al.	N/A	N/A
7547640	12/2008	Abatchev et al.	N/A	N/A
7560390	12/2008	Sant et al.	N/A	N/A
7563712	12/2008	Jung	N/A	N/A
7576010	12/2008	Lee et al.	N/A	N/A
7579278	12/2008	Sandhu	N/A	N/A
7611944	12/2008	Tran et al.	N/A	N/A
7611980	12/2008	Wells et al.	N/A	N/A
7629693	12/2008	Abatchev et al.	N/A	N/A
7648919	12/2009	Tran et al.	N/A	N/A
7651951	12/2009	Tran et al.	N/A	N/A
7655387	12/2009	Sandhu et al.	N/A	N/A
7666578	12/2009	Fischer et al.	N/A	N/A
7687408	12/2009	Abatchev et al.	N/A	N/A
7709390	12/2009	Olson	N/A	N/A
7718540	12/2009	Tran et al.	N/A	N/A
7732343	12/2009	Niroomand et al.	N/A	N/A
7759197	12/2009	Tran	N/A	N/A
7776683	12/2009	Tran et al.	N/A	N/A
7776744	12/2009	Sandhu et al.	N/A	N/A
7790531	12/2009	Tran	N/A	N/A
7808053	12/2009	Haller et al.	N/A	N/A
7829262	12/2009	Tran	N/A	N/A
7884022	12/2010	Bai et al.	N/A	N/A
7902074	12/2010	Niroomand et al.	N/A	N/A
7968403	12/2010	Ireland et al.	N/A	N/A
7993957	12/2010	Bez et al.	N/A	N/A
8003310	12/2010	Sandhu et al.	N/A	N/A
8003542	12/2010	Sant et al.	N/A	N/A
8012674	12/2010	Fischer et al.	N/A	N/A
8030222	12/2010	Tran et al.	N/A	N/A
8039399	12/2010	Niroomand et al.	N/A	N/A
8043915	12/2010	Tran	N/A	N/A
8048812	12/2010	Tran et al.	N/A	N/A
8053899	12/2010	Rhodes	N/A	N/A
8076208	12/2010	Smith	N/A	N/A

8119535	12/2011	Tran et al.	N/A	N/A
8158476	12/2011	Tran et al.	N/A	N/A
8173550	12/2011	Sant et al.	N/A	N/A
8207576	12/2011	Tran et al.	N/A	N/A
8216949	12/2011	Abatchev et al.	N/A	N/A
8334211	12/2011	Kewley	N/A	N/A
8338085	12/2011	Sandhu et al.	N/A	N/A
8389383	12/2012	Hopkins	N/A	N/A
8390034	12/2012	Tran	N/A	N/A
8426118	12/2012	Tran	N/A	N/A
8431971	12/2012	Tran	N/A	N/A
8450829	12/2012	Fischer et al.	N/A	N/A
8507341	12/2012	Tran et al.	N/A	N/A
8557704	12/2012	Wells et al.	N/A	N/A
8563229	12/2012	Tran	N/A	N/A
8593001	12/2012	Hopkins	N/A	N/A
8598041	12/2012	Sant et al.	N/A	N/A
8598632	12/2012	Tran et al.	N/A	N/A
8609324	12/2012	Tran	N/A	N/A
8674512	12/2013	Sandhu et al.	N/A	N/A
8859362	12/2013	Tran	438/296	H01L 21/30604
8865598	12/2013	Sant et al.	N/A	N/A
8883644	12/2013	Wells et al.	N/A	N/A
8889020	12/2013	Kewley	N/A	N/A
8921034	12/2013	Hopkins	N/A	N/A
8928111	12/2014	Smith	N/A	N/A
8932960	12/2014	Tran	N/A	N/A
8980756	12/2014	Tran	438/735	H01L 21/0337
9035416	12/2014	Fischer et al.	N/A	N/A
9048194	12/2014	Zhu	N/A	N/A
9099314	12/2014	Sandhu et al.	N/A	N/A
9117766	12/2014	Sant	N/A	H01L 21/0337
9147608	12/2014	Tran et al.	N/A	N/A
9184159	12/2014	Niroomand et al.	N/A	N/A
9412591	12/2015	Tran	N/A	H01L 21/0274
9412594	12/2015	Tran et al.	N/A	N/A
9478497	12/2015	Wells et al.	N/A	N/A
9553082	12/2016	Kewley	N/A	N/A
9666695	12/2016	Tran	N/A	N/A
9941155	12/2017	Tran	N/A	N/A
10497611	12/2018	Tran	N/A	N/A
10522348	12/2018	Tran et al.	N/A	N/A
2001/0013612	12/2000	Tran et al.	N/A	N/A
2001/0036743	12/2000	Sandhu	N/A	N/A
2001/0036745	12/2000	Sandhu	N/A	N/A
2002/0123226	12/2001	Trapp	N/A	N/A
2003/0001182	12/2002	Tran et al.	N/A	N/A
2003/0067017	12/2002	Ieong et al.	N/A	N/A
2003/0102515	12/2002	Tran et al.	N/A	N/A
2005/0029619	12/2004	Forbes	N/A	N/A

2005/0087842	12/2004	Forbes	N/A	N/A
2005/0161721	12/2004	Iyer et al.	N/A	N/A
2006/0003182	12/2005	Lane	428/688	H01L 21/0338
2006/0046200	12/2005	Abatchev et al.	N/A	N/A
2006/0046201	12/2005	Sandhu et al.	N/A	N/A
2006/0046407	12/2005	Juengling	N/A	N/A
2006/0046422	12/2005	Tran	257/E21.68	H01L 21/0337
2006/0046483	12/2005	Abatchev et al.	N/A	N/A
2006/0046484	12/2005	Abatchev et al.	N/A	N/A
2006/0208282	12/2005	Tran et al.	N/A	N/A
2006/0211260	12/2005	Tran	257/E21.235	H01L 21/3086
2006/0216922	12/2005	Tran et al.	N/A	N/A
2006/0216923	12/2005	Tran et al.	N/A	N/A
2006/0228854	12/2005	Tran et al.	N/A	N/A
2006/0240362	12/2005	Sandhu et al.	N/A	N/A
2006/0258109	12/2005	Juengling	N/A	N/A
2006/0258162	12/2005	Abatchev et al.	N/A	N/A
2006/0262511	12/2005	Abatchev et al.	N/A	N/A
2006/0263699	12/2005	Abatchev et al.	N/A	N/A
2006/0264000	12/2005	Tran et al.	N/A	N/A
2006/0264001	12/2005	Tran et al.	N/A	N/A
2006/0264002	12/2005	Tran et al.	N/A	N/A
2006/0267152	12/2005	Forbes	N/A	N/A
2006/0273456	12/2005	Sant et al.	N/A	N/A
2006/0281266	12/2005	Wells	N/A	N/A
2007/0045712	12/2006	Haller et al.	N/A	N/A
2007/0048674	12/2006	Wells	N/A	N/A
2007/0049011	12/2006	Tran	N/A	N/A
2007/0049030	12/2006	Sandhu et al.	N/A	N/A
2007/0049032	12/2006	Abatchev et al.	N/A	N/A
2007/0049035	12/2006	Tran	N/A	N/A
2007/0049040	12/2006	Bai et al.	N/A	N/A
2007/0117310	12/2006	Bai et al.	N/A	N/A
2007/0128856	12/2006	Tran et al.	N/A	N/A
2007/0138526	12/2006	Tran et al.	N/A	N/A
2007/0148984	12/2006	Abatchev et al.	N/A	N/A
2007/0161251	12/2006	Tran et al.	N/A	N/A
2007/0190463	12/2006	Sandhu et al.	N/A	N/A
2007/0224823	12/2006	Sandhu	N/A	N/A
2007/0238299	12/2006	Niroomand et al.	N/A	N/A
2007/0238308	12/2006	Niroomand et al.	N/A	N/A
2007/0249170	12/2006	Kewley	N/A	N/A
2007/0261016	12/2006	Sandhu et al.	N/A	N/A
2007/0264830	12/2006	Huang et al.	N/A	N/A
2007/0281219	12/2006	Sandhu	N/A	N/A
2008/0001187	12/2007	Booth et al.	N/A	N/A
2008/0008969	12/2007	Zhou et al.	N/A	N/A
2008/0014533	12/2007	Keller et al.	N/A	N/A
2008/0057692	12/2007	Wells et al.	N/A	N/A
2008/0070165	12/2007	Fischer et al.	N/A	N/A

2008/0085612	12/2007	Smythe et al.	N/A	N/A
2008/0122125	12/2007	Zhou	N/A	N/A
2008/0162781	12/2007	Haller et al.	N/A	N/A
2008/0176406	12/2007	Ikeda et al.	N/A	N/A
2008/0220600	12/2007	Alapati et al.	N/A	N/A
2008/0280212	12/2007	Kumar	N/A	N/A
2008/0299774	12/2007	Sandhu	N/A	N/A
2009/0035584	12/2008	Tran et al.	N/A	N/A
2009/0053892	12/2008	Meyer et al.	N/A	N/A
2009/0152645	12/2008	Tran	N/A	N/A
2009/0258492	12/2008	Sant et al.	N/A	N/A
2010/0003797	12/2009	Smith	N/A	N/A
2010/0029081	12/2009	Wells et al.	N/A	N/A
2010/0092890	12/2009	Sandhu et al.	N/A	N/A
2010/0092891	12/2009	Tran et al.	N/A	N/A
2010/0112489	12/2009	Fischer et al.	N/A	N/A
2010/0203727	12/2009	Abatchev et al.	N/A	N/A
2010/0210111	12/2009	Tran et al.	N/A	N/A
2010/0243161	12/2009	Tran	N/A	N/A
2010/0289070	12/2009	Tran	N/A	N/A
2011/0269252	12/2010	Sant et al.	N/A	N/A
2011/0291224	12/2010	Fischer et al.	N/A	N/A
2012/0044735	12/2011	Tran et al.	N/A	N/A
2012/0061807	12/2011	Tran	N/A	N/A
2012/0074500	12/2011	Smith	N/A	N/A
2012/0202350	12/2011	Sant et al.	N/A	N/A
2012/0256309	12/2011	Tran et al.	N/A	N/A
2013/0105937	12/2012	Niroomand et al.	N/A	N/A
2013/0105976	12/2012	Sandhu et al.	N/A	N/A
2013/0161799	12/2012	Hopkins	N/A	N/A
2013/0171784	12/2012	Tran	N/A	N/A
2013/0256827	12/2012	Fischer et al.	N/A	N/A
2013/0323929	12/2012	Zhu	N/A	N/A
2014/0038416	12/2013	Wells et al.	N/A	N/A
2014/0087563	12/2013	Sant et al.	N/A	N/A
2014/0091434	12/2013	Hopkins	N/A	N/A
2015/0024602	12/2014	Sant et al.	N/A	N/A
2015/0054168	12/2014	Wells et al.	N/A	N/A
2015/0123185	12/2014	Tran	N/A	N/A
2015/0170905	12/2014	Tran et al.	N/A	N/A
2016/0225634	12/2015	Anderson et al.	N/A	N/A
2017/0250110	12/2016	Tran	N/A	N/A
2018/0211868	12/2017	Tran	N/A	N/A
2020/0066578	12/2019	Light	N/A	H01L 21/0338
2020/0090929	12/2019	Tran et al.	N/A	N/A

OTHER PUBLICATIONS

International Report on Patentability for International Application No. PCT/US2008/070407, issued Feb. 2, 2010. cited by applicant

International Search Report for International Application No. PCT/US2008/070407, dated Feb. 11,

2009, 3 pages. cited by applicant
Lam Research Corporation; Technical Glossary #C; 1 page; <https://www.lamresearch.com/technical-glossary/#C>; definition of conformal, as of Jun. 17, 2019. cited by applicant
Tran et al., U.S. Appl. No. 60/666,031 entitled Integrated Circuit Fabrication, filed Mar. 28, 2005. cited by applicant
Written Opinion for International Application No. PCT/US2008/070407, dated Feb. 11, 2009, 4 pages. cited by applicant

Primary Examiner: Miller; Jami Valentine

Attorney, Agent or Firm: TraskBritt

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 16/692,440, filed Nov. 22, 2019, now U.S. Pat. No. 11,348,788 issued May 31, 2022, which is a continuation of U.S. patent application Ser. No. 16/249,369, filed Jan. 16, 2019, now U.S. Pat. No. 10,522,348, issued Dec. 31, 2019, which is a divisional of U.S. patent application Ser. No. 14/635,023, filed Mar. 2, 2015, now abandoned, which is a divisional of U.S. patent application Ser. No. 11/830,449, filed Jul. 30, 2007, now U.S. Pat. No. 8,980,756, issued Mar. 17, 2015, the disclosure of each of which is hereby incorporated herein in its entirety by this reference.

TECHNICAL FIELD

(1) Embodiments of the invention relate generally to integrated circuit device fabrication and, more particularly, to patterning techniques utilizing pitch reduction to fabricate a portion of the device, and associated structures.

BACKGROUND

(2) As a consequence of many factors, including demand for increased portability, computing power, memory capacity and energy efficiency, electronic devices such as integrated devices, are continuously being reduced in size. The sizes of the constituent features that form the devices, e.g., electrical elements and interconnect lines, are also constantly being decreased to facilitate this size reduction.

(3) The trend of decreasing feature size is evident, for example, in memory devices or devices such as dynamic random access memories (DRAM), Flash memory, static random access memories (SRAM), ferroelectric (FE) memories, etc. To take one example, DRAM may comprise thousands to billions of identical device components in the form of memory cells. By decreasing the sizes of the electrical device structures that comprise a memory cell and the widths and lengths of the conducting lines to access the memory cells, the memory devices can be made smaller. Additionally, storage capacities can be increased by fitting more memory cells on a given area in the memory devices.

(4) The continual reduction in feature sizes places ever greater demands on the techniques used to form the features. For example, photolithography is commonly used to pattern features, such as conductive lines and pads. The concept of pitch can be used to describe the sizes of these features. Pitch may be defined as the distance between identical points in two neighboring features. These features are typically defined by spaces between adjacent features, which spaces are typically filled by a material, such as an insulator. As a result, pitch can be viewed as the sum of the width of a feature and of the width of the space on one side of the feature separating that feature from a neighboring feature. However, due to factors such as limitations of optics and usable light or other

radiation wavelengths, photolithography techniques each have a minimum achievable pitch, below which a particular photolithographic technique cannot reliably form features. Thus, the minimum pitch of a photolithographic technique is an obstacle to continued feature size reduction.

(5) “Pitch doubling” or “pitch multiplication” is one method for extending the capabilities of photolithographic techniques beyond their minimum pitch. One pitch multiplication method is illustrated in FIGS. 1A-1F hereof and described in U.S. Pat. No. 5,328,810, issued to Lowrey et al., the entire disclosure of which is incorporated herein by reference. With reference to FIG. 1A, a pattern of lines **10** is photolithographically formed in a photo definable layer, such as a photoresist, which overlies a layer **20** of an expendable material, which in turn overlies a substrate **30**. As shown in FIG. 1B, the pattern is then transferred using an anisotropic etch to the layer **20** to form placeholders, or mandrels, **40**. The photoresist lines **10** can be stripped and the mandrels **40** can be isotropically etched to increase the distance between neighboring mandrels **40**, as shown in FIG. 1C. A layer **50** of spacer material is subsequently deposited over the mandrels **40**, as shown in FIG. 1D. Spacers **60**, i.e., the material extending or originally formed extending from sidewalls of another material, are then formed on the sides of the mandrels **40**. The spacer formation is accomplished by preferentially etching the spacer material from the horizontal surfaces **70** and **80** in a directional spacer etch, as shown in FIG. 1E. The remaining mandrels **40** are then removed, leaving behind only the spacers **60**, which together act as a mask for patterning, as shown in FIG. 1F. Thus, where a given pitch previously included a pattern defining one feature and one space, the same width now includes two features and two spaces, with the spaces defined by, e.g., the spacers **60**. As a result, the smallest feature size possible with a photolithographic technique is effectively decreased.

(6) While the pitch is actually halved in the example above, this reduction in pitch is conventionally referred to as pitch “doubling,” or, more generally, pitch “multiplication.” Thus, conventionally, “multiplication” of pitch by a certain factor actually involves reducing the pitch by that factor. The conventional terminology is retained herein.

(7) Because the layer **50** of spacer material typically has a single thickness **90** (see FIGS. 1D and 1E) and because the sizes of the features formed by the spacers **60** usually correspond to that thickness **90**, pitch doubling typically produces features of only one width. Devices, however, generally employ features of different sizes. For example, random access memory devices typically contain arrays of memory cells located in one, more central region of the active surface of the devices and logic devices located in the outer, so-called “peripheral” regions. In the arrays, the memory cells are connected by conductive lines and, in the periphery, the conductive lines contact landing pads for connecting arrays to logic. Peripheral features such as landing pads, however, may be larger than the conductive lines. In addition, periphery electrical devices, including peripheral transistors, may be larger than the electrical devices in the array. Moreover, even if peripheral features can be formed with the same pitch as features in the array, because mask patterns formed by pitch multiplication may be limited to those that are formed along the sidewalls of patterned photoresist, pitch multiplication by itself typically does not offer the flexibility, e.g., geometric flexibility, required to define some features, particularly when features vary in size above and below the pitch resolution of the photolithographic technique used.

(8) To overcome such limitations, some proposed methods for forming patterns at the periphery and in the array involve separately etching patterns into the array region and then peripheral region of a substrate. A pattern in the array region is first formed and transferred to the substrate or intermediate hard mask layer using one mask and then another pattern in the periphery region is formed and separately transferred to the substrate using another mask. Because such methods require forming the pattern in the array region first before forming the other pattern in the periphery region in order to thereafter transfer the patterns to the same level to be subsequently transferred to a substrate, such methods are limited in their ability to form equivalent or higher quality patterns suitable for forming the conductive lines of the array without additional masking and etching steps

required for forming the pattern for the periphery features if the array pattern is to be adequately protected. One limitation affecting the quality of the array pattern is defects. Defects may be caused, for example, by the photoresist material deposited between spacers so that features of a larger size may be formed in the periphery. Undesirably, the process conventionally used to form smaller, dimensionally critical, spacers in the pattern of the array while the other larger features in the pattern of the periphery are formed adds expense to the process flow without reducing defect potential in the array.

(9) In addition to problems encountered in forming differently sized features on an integrated circuit device, it has been found that conventional pitch-doubling techniques may experience difficulty transferring a pattern of spacers to a substrate. In conventional methods of transferring the pattern, both the spacers and the underlying substrate layer or layers are exposed to an etchant. The etchants, however, may also etch the material of the spacers, albeit at a slower rate. Thus, over the course of subsequently forming another pattern of features in a peripheral region of the same substrate and then transferring the patterns to an underlying material, the etchant used to form the pattern of features in the peripheral region may remove an unacceptable amount of the material of the spacers before the pattern transfer is completed in both central and peripheral regions.

(10) Also, a layer of material overlaid on the spacers while the features in the peripheral region are formed may leave residual material between adjacent spacers which may potentially cause defects or shorts therein which are subsequently transferred to one or more underlying layers. These difficulties are exacerbated by the trend towards decreasing feature size, which, for example, leads to the need to form trenches which have increasingly higher depth to width, or "aspect" ratios, increasing the potential for defects when subjected to additional steps in the process flow in order to obtain features of various sizes. Thus, in conjunction with difficulties in producing structures having different feature sizes, pattern transfer limitations make the application of pitch multiplication principles to integrated circuit device manufacture even more difficult.

(11) Accordingly, it would be desirable to provide enhanced methods of forming features of different sizes on semiconductor device structures, especially where some features are formed below the minimum size achievable using photolithographic and other conventional lithography techniques, and in conjunction with pitch multiplication.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIGS. 1A-1F show cross-sectional side views of a sequence of masking patterns for forming conductive lines in accordance with a conventional pitch doubling method.

(2) FIG. 2 shows a schematic top view of a partially formed semiconductor device, in accordance with embodiments of the invention.

(3) FIG. 3 shows a cross-sectional side view of a portion of the partially formed semiconductor device of FIG. 2, in accordance with embodiments of the invention.

(4) FIG. 4 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after forming a pattern of features in a selectively definable layer in the periphery of the device in accordance with embodiments of the invention.

(5) FIG. 5 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after transferring the pattern of features into a first hard mask layer in accordance with embodiments of the invention.

(6) FIG. 6 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after stripping off the material of the selectively definable layer in accordance with embodiments of the invention.

(7) FIG. 7 shows a cross-sectional side view of the portion of partially formed semiconductor

device of FIG. 2 after layering on another selectively definable layer over the pattern of features and upon a second hard mask layer in accordance with embodiments of the invention.

(8) FIG. 8 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after forming a pattern of lines in the another selectively definable layer in the array of the device in accordance with embodiments of the invention.

(9) FIG. 9 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after widening spaces between lines in the another selectively definable layer in accordance with embodiments of the invention.

(10) FIG. 10 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after depositing a layer of spacer material over the patterns in accordance with embodiments of the invention.

(11) FIG. 11 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after etching the layer of spacer material in accordance with embodiments of the invention.

(12) FIG. 12 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after etching the layer of spacer material and stripping the lines of the another selectively definable layer in accordance with embodiments of the invention.

(13) FIG. 13 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after depositing a protective layer of material over the patterns in accordance with embodiments of the invention.

(14) FIG. 14 shows a top view of the portion of partially formed semiconductor device of FIG. 2 after forming a protective mask in the protective layer of material over the patterns in accordance with embodiments of the invention.

(15) FIG. 15A shows a top view of the portion of partially formed semiconductor device of FIG. 2 after forming a “loop chop” etch of a pattern exposed by the protective mask in accordance with embodiments of the invention.

(16) FIG. 15B shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after stripping the material of the protective mask and the lines from the device providing a modified pattern in accordance with embodiments of the invention.

(17) FIG. 16 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after transferring the modified pattern to a primary hard mask layer ready for transferring into the substrate of the partially formed device.

(18) FIG. 17 shows a cross-sectional side view of the portion of partially formed semiconductor device of FIG. 2 after transferring the modified pattern to the substrate in accordance with embodiments of the invention.

(19) FIG. 18A shows conductive features in accordance with embodiments of the invention.

(20) FIG. 18B shows conductive features in accordance with embodiments of the invention.

DETAILED DESCRIPTION

(21) According to an embodiment of the invention, a method for semiconductor device fabrication by what may be termed “reverse pitch reduction flow” includes patterning a first pattern of features above a substrate and patterning a second pattern of pitch-multiplied spacers subsequent to patterning the first pattern of features. In embodiments of the invention, the first pattern of features may be formed using conventional lithography and the second pattern of pitch-multiplied spacers may be formed by a pitch multiplication technique. Embodiments of the invention also encompass structures associated with the methods disclosed.

(22) Embodiments of the invention may have particular utility in fabrication of NAND Flash devices, wherein the first pattern of features may comprise gates in a peripheral region of the device and the second pattern of features may comprise word lines in a central region thereof. Embodiments of the invention may also be employed in fabrication of DRAM memory, phase change memory and programmable gate array (PGA) devices.

(23) Reference will now be made to the Figures, wherein like numerals refer to like features and elements throughout. It will be appreciated that these Figures are not necessarily drawn to scale.

(24) In embodiments of the invention, a sequence of material layers is formed that allows formation of a mask for processing a substrate.

(25) FIG. 2 shows a top view of a portion of a partially formed integrated circuit device **100**. While the embodiments of the invention may be used to form any device, they are particularly advantageously applied to form devices having arrays of electrical devices, including memory cell arrays for volatile and non-volatile memory devices such as DRAM, ROM, phase change, or Flash memory, including NAND Flash memory, or integrated devices having logic or gate arrays. For example, the logic array may be a field programmable gate array (FPGA) having a core array similar to a memory array and a periphery with supporting logics. Also, the array may be a fine pitch repetitive logic circuitry or embedded memory on a processor, as additional examples. Consequently, the integrated circuit device **100** may be, e.g., a memory chip or a processor, which may include both a logic array and embedded memory, or any other integrated device having a logic or a gate array.

(26) The integrated circuit device **100** includes a central region **102**, which may be termed the “array,” at least partially bounded by a peripheral region **104**, which may be termed the “periphery.” It will be appreciated that, in a completed integrated circuit device, the array **102** will typically be densely populated with conducting lines and electrical devices such as transistors and capacitors. In a memory device, the electrical devices form a plurality of memory cells, which are conventionally arranged in a regular grid pattern at the intersections of word lines and bit lines. Desirably, pitch multiplication may be used to form features in the array **102**, as discussed below. On the other hand, the periphery **104** typically comprises features larger than those in the array **102**. Conventional photolithography, rather than pitch multiplication techniques, is generally used to pattern features, such as logic circuitry, in the periphery **104**, because the geometric complexity of logic circuits located in the periphery **104** makes using pitch multiplication difficult, whereas the regular grid typical of element patterns in the array **102** is conducive to pitch multiplication. In addition, some devices in the periphery require larger geometries due to electrical constraints, making pitch multiplication less advantageous than conventional photolithography for such devices. In addition to possible differences in relative scale, it will be appreciated by one of ordinary skill in the art that the relative positions, and the number, of periphery **104** and array **102** regions in the integrated circuit device **100** may vary from that depicted.

(27) FIG. 3 shows a cross-sectional side view of the partially formed integrated circuit device **100**. Various layers **120-150** are provided for masking above a substrate **110** comprising a layer of semiconductor material. In one NAND Flash embodiment, the substrate **110** may comprise a conventional polysilicon/WSi.sub.x/oxide gate stack or metal gate stack array. The layers **120-150** will be etched to form a mask for patterning the substrate **110**, as discussed below.

(28) The materials for the layers **120-150** overlying the substrate **110** are selectively chosen based upon consideration of the chemistry and process conditions for the pattern forming and pattern transferring steps discussed herein. Because the layers **120-150** between a topmost selectively definable layer **150** and the substrate **110** function to transfer a pattern derived from the selectively definable layer **150** to the substrate **110**, the layers **120-140** between the selectively definable layer **150** and the substrate **110** are chosen so that they may be selectively etched relative to other exposed materials. It will be appreciated that a material is considered selectively, or preferentially, etched when the etch rate for that material upon exposure to a given etchant is substantially greater, on the order of at least about 2-3 times greater to at least about 40 times greater than the etch rate for adjacent materials exposed to the same etchant. Because a function of the layers **130-150** overlying the primary hard mask layer **120** is to allow well-defined patterns to be formed in the primary hard mask layer **120**, it will be appreciated that one or more of the layers **130-150** may be omitted or substituted if suitable other materials, chemistries and/or process conditions are used.

(29) In the illustrated embodiment, the selectively definable layer **150**, which may comprise an optically or mechanically patternable layer overlies a hard mask, or etch stop, first hard mask layer **140**, which overlies a second hard mask layer **130**, which overlies the primary hard mask layer **120**, which overlies the substrate **110** to be processed (e.g., etched) through a mask. Beneficially, the mask through which the substrate **110** is processed is formed in the second hard mask layer **130** and/or in the primary hard mask layer **120**.

(30) With continued reference to FIG. **3**, the selectively definable layer **150** is photodefinable, e.g., formed of a photoresist, including any photoresist known in the art. For example, the photoresist may be any photoresist compatible with 157 nm, 193 nm, 248 nm or 365 nm wavelength systems, 193 nm wavelength immersion systems, extreme ultraviolet systems (including 13.7 nm wavelength systems) or electron beam lithographic systems. In addition, maskless lithography, or maskless photolithography, may be used to define the selectively definable layer **150**. Examples of photoresist materials include argon fluoride (ArF) sensitive photoresist, i.e., photoresist suitable for use with an ArF light source, and krypton fluoride (KrF) sensitive photoresist, i.e., photoresist suitable for use with a KrF light source. ArF photoresists are typically used with photolithography systems utilizing relatively short wavelength light, e.g., 193 nm. KrF photoresists are used with longer wavelength photolithography systems, such as 248 nm systems. In other embodiments, the primary hard mask layer **120** and any subsequent resist layers may be formed of a resist that may be patterned by nano-imprint lithography, e.g., by using a mold or mechanical force to pattern the resist. The selectively definable layer **150** will allow a first feature having a first size to be formed in the periphery **104**. It will be appreciated that light reflections may decrease the precision with which photolithography may define the edges of a pattern. Optionally, a bottom anti-reflective coating (BARC) (not shown) may similarly be used in addition to the first hard mask layer **140** to control light reflections.

(31) The material for the second hard mask layer **130**, which functions as an etch stop and exhibits anti-reflective properties, comprises an inorganic material. Suitable materials for second hard mask layer **130** include silicon oxide (SiO₂) or a deep ultra-violet (DUV) dielectric anti-reflective coating (DARC), such as a silicon-rich silicon oxynitride. In this embodiment of the invention, the second hard mask layer **130** is a dielectric anti-reflective coating (DARC). Using a DARC for the second hard mask layer **130** may be particularly advantageous for forming patterns having pitches near the resolution limits of a particular photolithographic technique. The DARC may enhance resolution by minimizing light reflections, thus increasing the precision with which photolithography may define the edges of a pattern. By way of nonlimiting example, the DARC layer may comprise a DUV DARC of about 200-400 Å (20-40 nm) thickness. Other suitable materials that exhibit adequate etch stop and anti-reflective properties may be used for the second hard mask layer **130**.

(32) In the illustrated embodiment, the hard mask or etch stop layer **140** is formed of silicon, e.g., poly amorphous silicon, or a film of another material that exhibits good etch selectivity to oxide. Other suitable materials for the first hard mask layer **140** may include a silicon oxide, e.g., a low silane oxide (LSO), low temperature nitride, and a thin layer of aluminum oxide, such as Al₂O₃. The LSO is formed by chemical vapor deposition using a relatively low silane flow and a relatively high N₂O precursor flow. Advantageously, such a deposition can be performed at relatively low temperatures, e.g., less than about 550° C., for example, less than about 400° C., to prevent damage to the underlying primary hard mask layer **120**, when the primary hard mask layer **120** is formed of a temperature-sensitive material. It will be appreciated that oxides may typically be etched with greater selectivity relative to silicon than nitrides. For example, conventional etch chemistries for oxides may remove the oxides at a rate more than 10 times faster than amorphous silicon, while conventional etch chemistries for nitrides typically only remove the nitrides at a rate of about three times faster than poly amorphous silicon. As a result, both the spacers (discussed below) and the second hard mask layer are preferably formed of the same

material, in the form of an oxide, when the first hard mask layer is formed of poly amorphous silicon.

(33) The primary hard mask layer **120** may be formed of amorphous carbon due to the excellent etch selectivity of this material relative to many other materials, including a very high etch selectivity relative to the hard mask materials. Further, the transparent carbon is a form of amorphous carbon that is highly transparent to light and that offers further improvements for photo alignment by being transparent to the wavelengths of light used for such alignment. Deposition techniques for forming such transparent carbon are known to those of ordinary skill in the art and, so, need not be further described. The amorphous carbon is particularly advantageous for transferring patterns to difficult-to-etch substrates, such as the substrate **110** comprising multiple materials or multiple layers of materials, or for forming small and high aspect ratio features therein.

(34) The combination of materials for the second and first hard mask layers **130** and **140** are selectably chosen based upon the material used to form a first feature in the periphery **104** in combination with providing the material used to form the spacers in the array **102** allowing transfer of the pattern or mask formed by the layers, as discussed below, into the underlying primary hard mask layer **120**. As previously mentioned, the primary hard mask layer **120** of the current embodiment is formed of amorphous carbon and selectively definable layer **150** is formed of photoresist. Optionally, other combinations of materials may be utilized to advantage, for example and without limitation, including (spacer material/first hard mask material/second hard mask material): oxide/amorphous silicon/oxide; nitride/amorphous silicon/oxide; nitride/oxide/amorphous silicon; amorphous silicon/oxide/amorphous silicon; carbon/amorphous silicon/oxide; and carbon/oxide/amorphous silicon. It will be appreciated that the oxide may be a form of silicon oxide and the nitride may be silicon nitride. Where the spacer material is oxide, as discussed below, the associated primary hard mask layer **120** is a material that is preferentially etchable relative to the oxide. For example, the primary hard mask layer **120** may be formed of a silicon-containing material. Depending on the selection of appropriate etch chemistries and neighboring materials; examples of other materials include amorphous carbon and etchable high dielectric materials.

(35) In addition to selecting appropriate materials for the various layers, the thicknesses of the layers **120-150** are selectively chosen depending upon compatibility with the etch chemistries and process conditions described herein. As discussed above, when transferring a pattern from an overlying layer to an underlying layer by selectively etching the underlying layer, materials from both layers are removed to some degree. Thus, the upper layer is sufficiently thick so that it is not removed over the course of the pattern transfer to the underlying layer but not so thick as to create an undesirable topography.

(36) In the illustrated embodiment, the selectively definable layer **150** is about 2000 angstroms ("Å") (200 nm) in thickness and, in other embodiments, may range in thickness from 500-3000 Å (50-300 nm). It is also recognized that the thickness of the selectively definable layer **150** may be to a greater or lesser extent than the 2000 Å illustrated. It will be appreciated that, in cases where the selectively definable layer **150** is a photoresist, the thickness of the selectively definable layer **150** may vary depending upon the wavelength of light used to pattern the primary hard mask layer **120**. A thickness of about 500-3000 Å (50-300 nm) thick and, more specifically, a thickness of about 2000-2500 Å (200-250 nm), is particularly advantageous for 248 nm wavelength systems.

(37) The hard mask layer **140** has a thickness of about 150-200 Å (20 nm) and, in other embodiments, may range in thickness to a greater or lesser extent than the 200 Å illustrated. One particularly suitable thickness is 100 Å. The first hard mask layer **140** may have a thickness ranging from about 100 Å (10 nm) to about 400 Å (40 nm). The second hard mask layer **130** is about 200-600 Å (20-60 nm) thick and, in other embodiments, may range in thickness to a greater or lesser extent. For example, the second hard mask layer **130** may have a thickness of about 300-500 Å (30-50 nm).

(38) As discussed above, the thickness of the primary hard mask layer **120** is chosen based upon the selectivity of the etch chemistry for etching the substrate and based upon the materials and complexity of the substrate. Advantageously, a thickness for primary hard mask layer **120** of about 3000 Å (300 nm) and, in other embodiments a thickness between 1000-5000 Å (100-500 nm) is particularly effective for transferring patterns to a variety of substrates, including substrates having a plurality of different materials to be etched during the transfer.

(39) Transferring patterns into a variety of substrates is readily accommodated when utilizing the primary hard mask layer **120** of sufficient thickness. For example, the illustrated substrate **110** comprising a plurality of layers (not shown) may be etched to form word lines over an array of gate stacks. The layers of the substrate **110** may include a tungsten silicide layer overlying a polysilicon layer, which overlies an oxide-nitride-oxide (ONO) composite layer, which overlies a polysilicon layer, the layers in combination and as previously processed comprising an array of gate stacks.

(40) The various layers discussed herein may be formed by various conventional methods. For example, spin-on-coating processes may be used to form photoresist, selectively definable layers. Various vapor deposition processes, such as chemical vapor deposition, may be used to form hard mask layers. Depositing each layer of materials may include depositing a material by coating, layering, or spinning, for example.

(41) A low temperature chemical vapor deposition (CVD) process may be used to deposit the hard mask layers or any other materials, e.g., spacer material described herein, over the primary hard mask layer **120**, especially in cases where the primary hard mask layer **120** is formed of amorphous carbon. Advantageously, it is known to those of ordinary skill in the art that the first and second hard mask layers **140** and **130** may be deposited at relatively low temperatures of less than about 550° C., lower than about 450° C., and even lower than about 400° C. Such low temperature deposition processes advantageously prevent chemical or physical disruption of the primary hard mask layer **120** made of amorphous carbon material. Various methods for forming these layers are known to those of ordinary skill in the art and are described in U.S. Pat. Nos. 7,115,525, 6,573,030, and U.S. Pat. Pub. No. 2006/0211260, the entire disclosures of each of which documents are incorporated herein by reference.

(42) After formation of the various layers **120-150** as described above, to improve and enhance the quality of a pattern of spacers formed by pitch multiplication, a first pattern of features is formed according to an embodiment of the invention. Then, a second pattern of spacers may be formed by pitch multiplication, followed by subjecting the patterns to a so-called “loop chop” process to eliminate closed loops formed in the mask. The pattern of features and the pattern of spacers at this point are consolidated for transferring into the substrate. The quality of the final structure formed within the substrate is improved by forming of the first pattern of features before forming the second pattern of spacers during a masking process. Specifically, as the second pattern of spacers is more sensitive to masking-related sensitivities and transferring processes than the first pattern of features, this process flow according to embodiments of the invention enables quality improvement in the second pattern of spacers by first subjecting the less dimensionally sensitive structures of the first pattern to the forming process.

(43) In accordance with an embodiment of the invention, a first pattern of features is formed principally in the periphery of the device. Each feature of the first pattern includes, particularly at minimum or larger critical dimensions that are directly formable in the photodefinable material of the selectively definable layer, and do not require a pitch reduction or multiplication technique as is required to obtain smaller critical dimensions of the spacers of the second pattern, as will be discussed below.

(44) With reference to FIG. 4, a first pattern **106** of features **105** is formed in the selectively definable layer **150**. The selectively definable layer **150** may be patterned by, e.g., photolithography, in which the selectively definable layer **150** is exposed to radiation through a reticle and then developed. After being developed, the remaining photodefinable material,

photoresist in this embodiment, comprises features **105** (only one feature shown for clarity). Each feature **105** of the first pattern **106** may form various landing pads, transistors and local interconnects, for example and without limitation, and generally may have a size larger than the smaller critical dimensions obtained with the spacers of the second pattern, as discussed below.

(45) After forming the first pattern **106**, the first hard mask layer **140** is etched to transfer the first pattern **106** formed in selectively definable layer **150** down to the hard mask layer **140** as shown in FIG. 5. The first hard mask layer **140**, formed of amorphous silicon, is anisotropically etched using, for example, an HBr and Cl.sub.2-containing plasma, and stopping the etch at the second hard mask layer **130**. This so called “dry” etch of the HBr and Cl.sub.2-containing plasma etches the amorphous silicon at a rate greater than about five times, and even as great as ten times, the rate at which the photoresist material of the features **105** may be etched. It is recognized that etching first hard mask layer **140** may consume some of the DARC material of the second hard mask layer **130**, for example, between 20-30 Å (4-5 nm), which may leave the surface of second hard mask layer **130** slightly nonuniform in topography. The uniformity of the second hard mask layer **130** is addressed below when forming the second pattern of spacers. HBr and Cl.sub.2 chemistry-based etchants exhibit good selectivity to oxide. Other suitable etchants may include C.sub.2F.sub.6/Cl.sub.2/O.sub.2, SF.sub.6, and CF.sub.4 for example and without limitation.

(46) With reference to FIG. 6, the first pattern **106** is cleaned while stripping the selectively definable layer **150**. The carbon material forming the photoresist selectively definable layer **150** and DARC second hard mask layer **130** may polymerize upon contact with etchants. For example, the HBr/Cl.sub.2 etch of the first hard mask layer **140** may cause parts of the layers **150** and **130** to polymerize and leave a residue around features **105** in the first hard mask layer **140**, causing a pattern having undesirably non-uniform features. Thus, the first pattern **106** is cleaned by stripping off organic material. The strip may be accomplished using, for example, an isotropic etch with O.sub.2 plasma or other etch processes recognized as suitable by a person of ordinary skill in the art for preserving the features **105'** in the hard mask layer **140**.

(47) Next, a second pattern of spacers is formed by pitch multiplication over the first pattern **106** of features **105'**. The second pattern comprises spacers having smaller critical dimensions than the first pattern **106** of features **105'** as formed. In addition, the second pattern may be formed completely, partially, or not overlapping the first pattern **106**.

(48) Turning to FIG. 7, to allow the second pattern to be formed, a selectively definable layer **160** is formed on, and overlies, the second hard mask layer **130** and first pattern **106** of features now formed in the first hard mask layer **140** to allow for patterning of the second pattern in the array **102**.

(49) As with the selectively definable layer **150**, the selectively definable layer **160** may be photodefinable, e.g., formed of a photoresist, including any suitable photoresist known in the art, such as a trimmable mandrel material. In addition, in other embodiments, the selectively definable layer **160** may be formed of a resist suitable for patterning by nano-imprint lithography.

(50) Optionally, while not necessarily required, a planar surface (not shown) may be formed prior to depositing the selectively definable layer **160** by depositing a planarizing material (not shown) around the features **105'** and upon the second hard mask layer **130** when required for improving the planarity of structure of the to-be-patterned array for forming spacers. Specifically, the planarizing layer may be employed where the resolution of the spacers to be formed in the second pattern may not be adequately defined without first providing a planarized surface. For example, a spin-on antireflective coating may be used for planarization purposes.

(51) With reference to FIG. 8, the selectively definable layer **160** is patterned using, e.g., the same photolithographic technique used to pattern the selectively definable layer **150**. Thus, a second pattern **108** is formed in the selectively definable layer **160**. Where the second pattern **108** is used to mask features in the array **102**, the area in the selectively definable layer **160** in the periphery **104** is preferably open, as illustrated. As noted above, however, while illustrated laterally adjacent

the first pattern **106**, the second pattern **108** may partially or completely overlap the first pattern **106** or be completely separated from the first pattern **106**. Thus, the use of different reference numerals (**106** and **108**) for these respective patterns indicates that they were originally formed in different acts.

(52) The process flow as described below results in the second pattern **108** that includes a pitch or feature size smaller than the minimum pitch or resolution of the photolithographic technique used in forming it, unlike the first pattern **106** that includes pitch or feature size equal to or greater than the minimum pitch or resolution of the photolithographic technique used to form the first pattern **106**. It will be appreciated that the second pattern **108** in the array **102** may be used to form arrays of conductive feeds, contacts and other semiconductor components when transferred into the substrate **110**, for example and without limitation.

(53) The second pattern **108** includes spaces or trenches **162**, which are delimited by photodefinable material features, or lines, **164** formed in the selectively photodefinable layer **160**. The trenches **162** may be formed by, for example, photolithography with 248 nm or 193 nm wavelengths light, in which the selectively definable layer **160** is exposed to radiation through a reticle and then developed as is known by a person of ordinary skill in the art. After being developed, the remaining photodefinable material, photoresist in the illustrated embodiment, forms mask features such as the array of photoresist lines **164** (shown in cross-section only) as illustrated.

(54) The resulting pitch of the photoresist lines **164** is equal to the sum of the width of a photoresist line **164** and the width of a neighboring space **162**. To minimize the critical dimensions of features formed using this pattern of photoresist lines **164** and spaces **162**, the pitch may be at or near the limits of the photolithographic technique used to pattern the selectively photodefinable layer **160**. For example, for photolithography utilizing 248 nm light, the pitch of the photoresist lines **164** can be about 1000 Å (100 nm). Thus, the pitch may be at the minimum pitch of the photolithographic technique and the spacer formed in the pattern as discussed below may advantageously have a pitch below the minimum pitch of the photolithographic technique.

(55) As shown in FIG. 9, the spaces **162** may be widened by etching the photoresist material of the photoresist lines **164**, to form modified spaces **162a** and photoresist lines **164a**. The photoresist lines **164** are etched using an isotropic etch to “shrink” those features. Suitable etches include etches using an oxygen-containing plasma, e.g., a SO₂/O₂/N₂/Ar plasma, a Cl₂/O₂/He plasma or an HBr/O₂/N₂ plasma. The extent of the etch is selected so that the widths of the photoresist lines **164a** are substantially equal to the desired spacing between the later-formed spacers (**172** in FIG. 11), as will be appreciated from the discussion below. For example, the width of the photoresist lines **164** may be reduced to 800-1200 Å (80-120 nm) or even further reduced to about 400-700 Å (40-70 nm). Advantageously, the width-reducing etch allows the photoresist lines **164a** to be narrower than would otherwise be possible using the photolithographic technique used to pattern the selectively definable layer **160**. In addition, the etch may smooth the edges by removing material of the photoresist lines **164a**, thus improving the line edge roughness uniformity of those lines. While the critical dimensions of the photoresist lines **164a** may be etched below the resolution limits of the photolithographic technique, it will be appreciated that this etch does not alter the pitch of the spaces **162a** and photoresist lines **164a**, since the distance between identical relative points in these features remains the same.

(56) Next, as shown in FIG. 10, a spacer layer **170** of spacer material is preferably blanket deposited conformally over exposed surfaces, including the second hard mask layer **130** and the top and sidewalls of the patterned, modified definable layer **160a**. The spacer material may be any material that can act as a mask for transferring a pattern to the underlying second hard mask layer **130**. The spacer material is selected for deposition with good step coverage, at a temperature compatible with the modified definable layer **160a**, and suitability for etching relative to the modified definable layer **160a** and the underlying second hard mask layer **130**. Materials for the spacer layer **170** may include silicon, silicon oxides and silicon nitrides. In the illustrated

embodiment, the spacer material is a silicon oxide deposited at a relatively low temperature, such as 75° C., which provides particular advantages in combination with other selected materials of the masking stack.

(57) Methods for depositing the material of the spacer layer **170** may include chemical vapor deposition, e.g., using O.sub.3 and TEOS to form silicon oxide, and atomic layer deposition, e.g., using a silicon precursor with an oxygen or nitrogen precursor to form silicon oxides and nitrides, respectively. The thickness of the spacer layer **170** is preferentially determined based upon the desired width of the spacers **172** (FIG. **11**). For example, in this embodiment, the spacer layer **170** is deposited to a thickness of about 200-800 Å (20-80 nm). In other embodiments, the spacer layer **170** may be deposited to a thickness ranging between 400-600 Å (40-60 nm). In still other embodiments, the layer may range between about 100-300 Å (10-30 nm) or to a greater or lesser extent than illustrated. The spacer layer **170** formed over the first pattern **106** of features **105'** in the periphery **104** of the circuit device **100** may see uneven steps ranging about 250 Å (25 nm) in size, which will be stripped away when forming the spacers **172** as shown in FIG. **11** without substantial alteration of the features **105'** as formed.

(58) Turning now to FIG. **11**, the spacers **172** are now formed in the second pattern **108** by exposing the silicon oxide material of the spacer layer **170** to an anisotropic etch to remove spacer material from horizontal surfaces **180** of the partially formed circuit device **100** while stopping on the surface of the first hard mask layer **140** and the second hard mask layer **130**. Such an etch, also known as “spacer etch,” may be performed using a fluorocarbon plasma containing, for example and without limitation, CF.sub.4/CHF.sub.3, C.sub.4F.sub.8/CH.sub.2F.sub.2 or CHF.sub.3/Ar plasma. The material of the modified definable layer **160a** may be selectively retained between adjacent spacers **172** while further processing to remove portions of the spacer material is performed in accordance with embodiments of the invention as described below. Beneficially, retaining the material used to form the photoresist lines **164a** of the modified definable layer **160a** between adjacent spacers **172** enhances the quality of a portion of the spacers **172** by not subjecting the material to extra processing or cleaning steps that may undesirably erode or otherwise damage or displace the spacers prior to their ultimate pattern transfer to the underlying substrate **110**.

(59) Optionally, in other embodiments of the invention as shown in FIG. **12**, the modified definable layer **160a** may be removed to leave the spacers **172** in freestanding alignment. In such an instance, the modified definable layer **160a** may be selectively removed using an organic strip process as described above. Optional etch chemistries may include an oxygen-containing plasma etch, such as etching using an O.sub.2 plasma strip.

(60) Thus, pitch reduction or multiplication for spacers **172** has been accomplished. In the illustrated embodiment, the pitch of the spacers **172** is roughly half that of the photoresist lines **164** and spaces **162** (FIG. **8**) originally formed by photolithography. Where the photoresist lines **164** had a pitch of about 2000 Å (200 nm), spacers **172** having a pitch of about 1000 Å (100 nm) or less may be formed. It will be appreciated that, because the spacers **172** are formed on opposing sidewalls of each of the features or photoresist lines **164a**, the spacers **172** generally follow the outline of the pattern of features or photoresist lines **164a** in the modified photodefinable layer **160a** and, so, form a closed loop around the ends of the photoresist lines **164a**. The spacers **172** form relatively smaller features of the second pattern **108** that may be transferred to the underlying substrate **110** together with the relatively larger features **105'** forming the first pattern **106**.

Advantageously, the first pattern **106** and the second pattern **108** may now be subjected to so-called “loop chop” process to eliminate undesirable closed loops or other portions of pattern material before transferring the mask to the substrate **110**.

(61) Optionally, a second pattern of spacers may be formed after the first pattern of features is formed by utilizing other methods of pitch multiplication. Other methods of pitch multiplication may require layering different or select layers of material above the substrate in addition to the layers mentioned herein. For example, a method of forming a pattern of spacers by pitch

multiplication is described in paragraphs [0056]-[0092] and FIGS. 2A-10 of U.S. Pub. No. 2006/0046422 to Tran et al., dated Mar. 2, 2006, the entire disclosure of which is incorporated by reference herein.

(62) In methods according to embodiments of the invention, spacer material in the form of loops of spacer material connecting adjacent spacers **172** is etched to remove the loops and isolate the spacers **172**. This etch may be used to form two separate lines of spacers **172** initially connected at their adjacent ends by a loop of spacer material extending around the end of a photoresist line **164a** corresponding to two separate conductive paths to be formed in the substrate **110**. It will be appreciated that more than two lines may be formed, if desired, by etching the spacers **172** at more than two locations. Other suitable method for cutting off the ends of the loops is disclosed in U.S. Pub. No. 2006/0046422 to Tran et al., dated Mar. 2, 2006, the entire disclosure of which is incorporated by reference herein.

(63) To form the separate lines, a protective mask is formed over parts of the lines to be retained and the exposed, unprotected part of the loop of spacer material connecting the spacer lines are then etched. The protective mask is then removed to leave a plurality of physically separated and electrically isolated lines comprised of spacers **172**.

(64) With reference to FIG. **13**, a protective material forming a protective layer **181** is selectively deposited around and over the spacers **172** and the parts of the second hard mask layer **130** and selectively definable layer **160** forming the second pattern **108**, and, in this embodiment, is selectively deposited around and over the features **105'** forming the first pattern **106**. The material of the protective layer **181** may be a photodefinable material such as photoresist as described above and is sufficiently thick to protect the underlying mask during the etch. Optionally, an anti-reflective coating ("ARC") (not shown) may be provided under the protective layer **181**, e.g., above the first and second patterns **106** and **108**, to improve photolithography results as understood by a person of ordinary skill in the art. The photoresist and the optional anti-reflective coating may be deposited using various methods known in the art, including spin-on-coating processes. With reference to FIG. **14**, a protective mask **182** is subsequently patterned in the protective layer **181**, e.g., by photolithography, to protect desired portions of the underlying first and second patterns **106** and **108** from a subsequent etch. It is recognized that the first pattern **106** forming the features **105'** may be entirely, partially or not covered depending upon the relative resistance to etching during the etch. To separate the spacers **172** of each loop into two separate lines, portions of the loops are exposed for etching in at least two separate locations. To simplify processing, the exposed portions of the loops are generally the ends of the loops formed by the spacers **172**, as illustrated.

(65) In other embodiments, it will be appreciated that the protective layer **181** may be formed of any material that may be selectively removed, e.g., relative to the spacers **172**, the layers **130**, **140**, **160a**, and **170**. In those cases, the protective mask **182** may be formed in another material, e.g., photoresist, overlying the protective layer **181**.

(66) Advantageously, where the ends of the spacers **172** extend in a straight line, the length and simple geometry of the straight lines may minimize the precision required for forming the protective mask **182**; that is, the protective mask need only be formed so that it leaves the ends of the spacers **172** exposed. Thus, by centering the mask a selected distance from the ends of the spacers **172**, a misaligned mask may cause slightly more or less of the spacers **172** to be exposed, but may still accomplish the objective of leaving the ends adequately exposed. While the margin of error for aligning the protective mask **182** is larger than if the protective mask **182** were required to form a geometrically complex shape, it is recognized that other shapes may be formed in the protective mask **182** different from the rectangular shape of the protective mask **182** as illustrated. See, for example, U.S. Pub. No. 2006/0046422 to Tran et al., the disclosure of which is incorporated herein in its entirety by reference.

(67) With reference to FIG. **15A**, the exposed portions of the spacers **172** are etched away leaving the exposed portions of the photoresist lines **164a** and the features **105'** of pattern **106**. Where the

spacers **172** are formed from silicon oxide or nitride, suitable etch chemistries may include a fluorocarbon etch or in the case of spacers **172** formed of an oxide, such as silicon oxide, the exposed loops of the spacers **172** may be isotropically etched using a wet chemistry, for example, a buffered oxide etch. One suitable etchant for a silicon dioxide spacer material is an HF/H₂O wet etch at a 500:1 dilution ratio. After being etched, the spacers **172** no longer form a loop with a neighboring spacer **172** as illustrated. The spacers **172** as etched thus forms a modified pattern **109** of features **105'** and spacers **172** with the material of the protective mask **182** removed. FIG. **15B** shows a side view of the resulting structure, taken along the vertical plane as indicated in FIG. **15A** with the material of the photoresist lines **164a** removed.

(68) Optionally, where the protective mask **182** is sufficiently thick and the photoresist lines **164a** were not previously removed, the exposed portions of the photoresist lines **164a** may be descummed or etched away in order to facilitate etching the exposed portions of the spacers **172**. For example, an O₂/N₂ reactive ion etch, an O₂ etch, or a CF₄ and/or CHF₃ plasma etch may be employed. Also, the exposed surface of the partially fabricated circuit device **100**, i.e., the portion not protected by the protective mask **182**, may be cleaned prior to the etching the exposed portions of the spacers **172**.

(69) With reference to FIGS. **15A** and **15B**, the materials of the protective mask **182** and of the photoresist lines **164a** are selectively removed. Where the material is photoresist or optional ARC, etch chemistries include anisotropic etches, such as with an SO₂-containing plasma. In other embodiments, the mask of the partially formed circuit device **100** may be subjected to an ashing process to remove the material of protective layer **181** and selectively definable layer **160** where the material of the modified pattern **109** is compatible with the ashing process. It will be appreciated that the spacers **172** and the features **105'** are not attacked during this removal act and that the primary hard mask layer **120** is protected by the second hard mask layer **130**.

Advantageously, by selectively removing the material of the photoresist lines **164a** together with the material of the protective mask **182**, the inner portions of the spacers **172** are subjected to less processing than would be if the material of the photoresist lines **164a** was removed prior to the “loop chop” process, beneficially enhancing resolution and reducing variations and defects when the modified pattern **109** is transferred to the underlying substrate **110**.

(70) According to embodiments of the invention, the modified pattern **109** comprising the spacers **172** and the features **105'** of the patterns **108** and **106**, respectively, may be simultaneously transferred to the substrate **110**.

(71) With reference to FIG. **16**, the second hard mask layer **130** and the primary hard mask layer **120** are etched to transfer the modified pattern **109** down to the primary hard mask layer **120**, to form a pattern of components of mixed feature size in the primary hard mask layer **120**.

(72) Optionally, before transferring the modified pattern into the hard mask layers **120** and **130**, the modified pattern **109** is cleaned. As noted above, the carbon material forming the layers **130** and **181** may polymerize upon contact with etchants, leaving a residue around features or spacers on the second hard mask layer **130**, causing a modified pattern **109** having undesirably non-uniform feature sizes. Thus, the modified pattern **109** is cleaned by stripping off an organic material. The cleaning may be accomplished using, e.g., an isotropic etch with O₂ plasma and may be done simultaneously while stripping of the protective mask **182**. For example, O₂ wet clean with an H₂O, H₂O₂, NH₄OH or so-called “SCI” solution.

(73) Turning to FIG. **16**, the modified pattern **109** is transferred to the primary hard mask layer **120**. The transfer is accomplished by anisotropically etching the second hard mask layer **130** and the primary hard mask layer **120**, using an SO₂-containing plasma. Other suitable etch chemistries include a Cl₂/O₂, HBr/O₂/N₂ or SiCl₄/O₂/N₂/HBr or SiCl₄/O₂-containing plasma. As noted above, the SO₂-containing plasma is particularly suitable as it has been found to have excellent selectivity for the amorphous carbon of the primary hard mask layer **120** and the DARC of the second hard mask layer **130** relative to the

material of the spacers **172** and the features **105'**. Thus, a thick enough mask may be formed in the primary hard mask layer **120** to later effectively transfer the mask pattern to the substrate **110**, particularly through multiple materials of the substrate using selective etch chemistries and without wearing away the primary hard mask layer **120** before the pattern transfer is complete.

(74) After the modified pattern **109** is transferred to the primary hard mask layer **120**, the modified pattern **109** is transferred to the substrate **110** using the patterned primary hard mask layer **120** as a mask as shown in FIG. **17**. Given the disparate materials used for the primary hard mask layer **120** and the substrate **110** (e.g., amorphous carbon and silicon or silicon compounds, respectively), the pattern transfer can be readily accomplished using conventional etch chemistries appropriate for etching the material or materials of the substrate **110** to form the final structures therein. The process used to transfer the modified pattern **109** from the primary hard mask layer **120** and into the substrate **110** may include any suitable process known to a person of ordinary skill in the art.

(75) The spacers **172** and the features **105'** of the modified pattern **109** may be employed to respectively form interconnect lines such as word lines and associated integrated device features, such as landing pads as transferred into the substrate. Methods for forming interconnects and landing pads are disclosed in U.S. Pub. No. 2006/0046422 to Tran et al., dated Mar. 2, 2006, the entire disclosure of which was previously incorporated herein by reference. Other methods for forming interconnects and landing pad are disclosed in U.S. Pat. No. 7,115,525 to Abatchev et al., dated Oct. 3, 2006, and U.S. Pub. No. 2006/0211260 to Tran et al., dated Sep. 21, 2006, the entire disclosures of which are incorporated herein by reference.

(76) It will also be appreciated that the pitch of the second pattern **108** may be more than doubled as is shown in the drawing figures herein, particularly before the modified pattern **109** is transferred to the substrate. For example, the second pattern **108** may be further pitch multiplied by forming spacers around the spacers **172**, then removing the spacers **172**, then forming spacers around the spacers that were formerly around the spacers **172**, and so on. For example, a method for further pitch multiplication is discussed in U.S. Pat. No. 5,328,810 to Lowrey et al., the entire disclosure of which is incorporated herein by reference. In addition, while embodiments of the invention may advantageously be applied to form a modified pattern **109** having both pitch multiplied and conventionally photolithographically defined features, the first and second patterns **106** and **108** may both be pitch multiplied or may have different degrees of pitch multiplication.

(77) In addition, the embodiments of the invention may be employed multiple times throughout an integrated device fabrication process to form pitch multiplied features and conventional features in a plurality of layers or vertical levels, which may be vertically contiguous or non-contiguous and vertically separated. In such cases, each of the individual levels to be patterned would constitute a substrate **110** and the various layers **120-181** may be formed over the individual level to be patterned. It will also be appreciated that the particular composition and height of the various layers **120-181** discussed above may be varied depending upon a particular application. In one regard, the primary hard mask layer **120** may be sufficiently thin in order to provide structural stability to the mask, to protect the substrate material throughout fabrication, and to allow the mask to be transferred into the substrate **110** without complete removal of the material of the primary hard mask layer **120** before the final etch is finished. For example, the thickness of the primary hard mask layer **120** may be varied depending upon the identity of the substrate **110**, e.g., the chemical composition of the substrate, whether the substrate comprises single or multiple layers of material, the depth of features to be formed, for example, and the available etch chemistries, without limitation. In some cases, one or more layers of layers **120-181** may be omitted or more layers may be added. For example, the primary hard mask layer **120** may be omitted in cases where the second hard mask layer **130** is sufficiently durable to adequately transfer a modified pattern **109** to the substrate **110**.

(78) Also, while “processing” through the various mask layers involves etching an underlying layer, processing through the mask layers may involve subjecting layers underlying the mask layers

to any semiconductor fabrication process. For example, processing may involve ion implantation, diffusion doping, depositing, or wet etching, without limitation, through the mask layers and onto underlying layers. In addition, the mask layers may be used as a stop or barrier for chemical mechanical polishing (CMP) or CMP may be performed on any of the layers to allow for both planarization and etching of the underlying layers, as disclosed in U.S. Provisional Patent Application No. 60/666,031, filed Mar. 28, 2005, the entire disclosure of which is incorporated by reference herein.

(79) It will be appreciated that the “substrate” to which patterns are transferred may include a layer of a single material, a plurality of layers of different materials, a layer or layers having regions of different materials or structures in them, etc. These materials may include semiconductors, insulators, conductors, or combinations thereof. For example, the substrate may comprise doped polysilicon, an electrical device active area, a silicide, or a metal layer, such as a tungsten, aluminum or copper layer, or combinations thereof. In some embodiments, the mask features discussed herein may directly correspond to the desired placement of conductive features **190**, such as interconnects, in the substrate, as shown in FIG. **18A**. In other embodiments, the substrate may be an insulator and the location of mask features may correspond to the desired location of insulators, such as in damascene metallization, as shown in FIG. **18B**. Examples of structures formed in the substrate include gate stacks and shallow trench isolation structures.

(80) Further, in any of the acts described herein above, transferring a pattern from an overlying level to an underlying level involves forming features or spacers in the underlying level that generally correspond to features or spacers in the overlying level. For example, the path of lines in the underlying level will generally follow the path of lines in the overlying level and the location of other features in the underlying level will correspond to the location of similar features or spacers in the overlying level. The precise shapes and sizes of features and spacers may vary from the overlying level to the underlying level, however. For example, depending upon etch chemistries and conditions, the sizes of and relative spacing between the features and spacers forming the transferred patterns may be enlarged or diminished relative to the pattern on the overlying level, while still resembling the same initial “pattern,” as are seen from the example of shrinking the lines in the embodiments described above. Thus, even with some changes in the dimensions of features or spacers, the transferred pattern, or patterns, is still considered to be the same pattern, or patterns, as the initial pattern. In contrast, forming spacers around mask features, e.g., the lines, may change the pattern.

CONCLUSION

(81) Embodiments of the invention provide reverse pitch reduction flow enabling improved pattern transfer and the formation of differently sized features in conjunction with the use of pitch multiplication.

(82) In methods according to embodiments of the invention, a sequence of layers of materials is formed that allow formation of a mask for processing a substrate to fabricate, for example, a memory chip or other integrated circuit device incorporating at least two regions on the active surface thereof having structural elements of substantially differing feature size. Thereafter, a first pattern of features is formed where conventional photolithography may be used to form the first pattern defining features in the mask, the features being generally formed in one region of the device, e.g., the peripheral region of the memory chip. Subsequently, a second pattern of spacers is formed using pitch multiplication. The second pattern of spacers form an element array in another region of the device, e.g., the memory array of the memory chip, advantageously eliminating acts conventionally required to form the spacers when subsequent features of various sizes are required to be formed therewith. The quality of the pattern of spacers may be improved and enhanced for subsequent transfer to the underlying substrate while potentially eliminating additional layering, cleaning, and etching acts otherwise conventionally required in order to form a device having respective features of diverse dimensions in the region of the memory array and in the peripheral

region. The second pattern may completely or partially overlap the first pattern, or, in some embodiments, may be completely formed in different regions of the device, e.g., the periphery of the memory chip. The first pattern and the second pattern may be selectively covered by a protective mask and subjected to a so-called “loop chop” process to eliminate undesirable closed loops in order to obtain a modified pattern for transfer to the substrate. Optionally, a “loop chop” may be omitted during fabrication for a particular polarity of a level, thus saving an additional masking step.

(83) Embodiments of the invention facilitate combining the patterns forming the differently sized spacers and features and successfully transferring the spacer and feature sizes and configurations to the underlying substrate while subjecting the spacers, with their size below the minimum pitch of the photolithographic technique used for patterning them, to fewer process acts which might compromise the quality of the transfer.

(84) In further embodiments of the invention, the pattern of pitch-multiplied resolution spacers may be configured as an array.

(85) While particular embodiments of the invention have been shown and described, numerous variations and other embodiments will occur to those of ordinary skill in the art. Accordingly, the invention is only limited in terms of the scope of the appended claims.

Claims

1. A method of forming an electronic device, comprising: forming a first pattern of features adjacent to one or more materials; forming a photoresist material over the first pattern of features; forming a second pattern of features through the photoresist material and laterally adjacent to the first pattern of features by removing portions of the photoresist material overlying the first pattern of features, the features of the second pattern having a lateral dimension relatively less than a lateral dimension of the features of the first pattern; and using a combined pattern of the first pattern of features and the second pattern of features to transfer the first pattern of features and the second pattern of features to the one or more materials.
2. The method of claim 1, further comprising: forming a hard mask over the one or more materials prior to forming the first pattern of features; and removing portions of the hard mask exposed through the combined pattern to transfer the first pattern of features and the second pattern of features to the one or more materials.
3. The method of claim 1, further comprising forming a protective mask over portions of the first pattern of features and the second pattern of features, wherein the photoresist material is substantially removed prior to forming the protective mask.
4. The method of claim 1, wherein forming the second pattern of features comprises: patterning the photoresist material to form lithographic features; removing additional portions of the photoresist material along opposing side surfaces of the lithographic features; and conformally forming a spacer material adjacent to remaining portions of the photoresist material.
5. The method of claim 1, wherein the combined pattern of the first pattern of features and the second pattern of features directly corresponds to positions of subsequently formed gate structures and conductive lines in the one or more materials.
6. The method of claim 5, wherein the conductive lines are centrally located within an array and the gate structures are laterally adjacent to the conductive lines within a periphery of the array.
7. The method of claim 1, further comprising forming openings in the one or more materials in a single material removal act using the combined pattern of the first pattern of features and the second pattern of features.
8. A method of forming an electronic device, comprising: forming a first pattern of features in a peripheral region laterally adjacent to a central region; forming a photoresist material over the first pattern of features; forming a second pattern of features through the photoresist material in the

central region; forming a mask material over the first pattern of features and the second pattern of features; and transferring the first pattern of features and the second pattern of features to one or more underlying materials to form conductive lines within the central region and periphery electrical structures within the peripheral region.

9. The method of claim 8, further comprising forming the second pattern of features after forming the first pattern of features, the features of the second pattern including segmented portions of the photoresist material.

10. The method of claim 8, wherein forming the second pattern of features comprises using spacers formed by pitch multiplication.

11. The method of claim 8, wherein forming the second pattern of features comprises: forming a conformal material adjacent to the photoresist material and the first pattern of features, a material composition of the conformal material differing from a material composition of the photoresist material; selectively removing portions of the conformal material; and substantially removing the photoresist material prior to forming the mask material.

12. The method of claim 8, wherein forming the mask material comprises centering the mask material over the first pattern of features and the second pattern of features while leaving end portions thereof exposed.

13. The method of claim 8, wherein transferring the first pattern of features and the second pattern of features to the one or more underlying materials comprises forming a modified pattern of the features of the second pattern to be relatively smaller than the features of the first pattern.

14. The method of claim 8, wherein forming the conductive lines comprises forming access lines, and wherein forming the periphery electrical structures comprises forming one or more of landing pads, transistors, and local interconnects.

15. A method of forming an electronic device, comprising: forming a selectively definable material over at least a portion of a peripheral region including segmented portions of a mask material; forming pitch-multiplied spacers using segmented portions of the selectively definable material within an array region, laterally adjacent and at least partially surrounded by the peripheral region; and forming openings in a semiconductive material to form electrical structures within the peripheral region and conductive lines within the array region using the segmented portions of the mask material combined with the pitch-multiplied spacers.

16. The method of claim 15, further comprising forming the mask material over the semiconductive material, and patterning the mask material to form the segmented portions of the mask material within the peripheral region prior to forming the selectively definable material.

17. The method of claim 15, further comprising: removing the segmented portions of the selectively definable material; and forming a protective mask material over the pitch-multiplied spacers.

18. The method of claim 15, wherein forming the pitch-multiplied spacers comprises enlarging initial openings between neighboring portions of the selectively definable material by laterally removing portions of the selectively definable material.

19. The method of claim 15, wherein forming the pitch-multiplied spacers comprises conformally forming a spacer material over the segmented portions of the selectively definable material, and selectively removing portions of the spacer material to separate the pitch-multiplied spacers from one another.
