

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12400984
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Huang; Sin-Yao et al.

Isolation structure for bond pad structure

Abstract

Various embodiments of the present disclosure are directed towards a method for forming an integrated chip including a substrate having an upper surface vertically below a top surface. A dielectric structure contacts the top surface of the substrate. A conductive structure is disposed in the substrate. The conductive structure includes an upper conductive body and conductive protrusions directly underlying the upper conductive body. The upper conductive body overlies the upper surface of the substrate. A bottom surface of the dielectric structure is disposed between a top surface and a bottom surface of the upper conductive body. An isolation structure is disposed in the substrate on opposing sides of the upper conductive body.

Inventors: Huang; Sin-Yao (Tainan, TW), Lin; Jeng-Shyan (Tainan, TW), Chou; Shih-Pei (Tainan, TW), Hsu; Tzu-Hsuan (Kaohsiung, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsin-Chu, TW)

Family ID: 1000008780615

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 18/318887

Filed: May 17, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230290749 A1	Sep. 14, 2023

Related U.S. Application Data

continuation parent-doc US 17236360 20210421 US 11694979 child-doc US 18318887
continuation parent-doc US 16532781 20190806 US 10991667 20210427 child-doc US 17236360

Publication Classification

Int. Cl.: **H01L23/00** (20060101); **H01L27/146** (20060101); **H10F39/00** (20250101); **H10F39/12** (20250101); **H10F39/18** (20250101)

U.S. Cl.:

CPC **H01L24/08** (20130101); **H01L24/03** (20130101); **H01L24/05** (20130101); **H10F39/011** (20250101); **H10F39/014** (20250101); **H10F39/026** (20250101); **H10F39/182** (20250101); **H10F39/199** (20250101); **H10F39/807** (20250101); **H10F39/811** (20250101); H01L24/13 (20130101); H01L2224/02233 (20130101); H01L2224/0225 (20130101); H01L2224/02251 (20130101); H01L2224/02255 (20130101); H01L2224/0226 (20130101); H01L2224/0345 (20130101); H01L2224/03462 (20130101); H01L2224/03464 (20130101); H01L2224/0361 (20130101); H01L2224/03622 (20130101); H01L2224/0401 (20130101); H01L2224/05553 (20130101); H01L2224/05554 (20130101); H01L2224/05557 (20130101); H01L2224/05559 (20130101); H01L2224/05571 (20130101); H01L2224/05624 (20130101); H01L2224/05647 (20130101); H01L2224/13007 (20130101); H01L2224/131 (20130101); H01L2924/00014 (20130101); H01L2924/053 (20130101); H10F39/8053 (20250101); H01L2224/02233 (20130101); H01L2924/00012 (20130101); H01L2224/05553 (20130101); H01L2924/00012 (20130101); H01L2224/05554 (20130101); H01L2924/00012 (20130101); H01L2224/05571 (20130101); H01L2924/00012 (20130101); H01L2224/05647 (20130101); H01L2924/00014 (20130101); H01L2224/131 (20130101); H01L2924/014 (20130101); H01L2924/00014 (20130101); H01L2224/05624 (20130101); H01L2924/01029 (20130101); H01L2224/0345 (20130101); H01L2924/00014 (20130101); H01L2224/03462 (20130101); H01L2924/00014 (20130101); H01L2224/03464 (20130101); H01L2924/00014 (20130101); H01L2224/03622 (20130101); H01L2924/00014 (20130101); H01L2224/0361 (20130101); H01L2924/00014 (20130101); H01L2224/0225 (20130101); H01L2924/00012 (20130101); H01L2224/0226 (20130101); H01L2924/05442 (20130101); H01L2224/0226 (20130101); H01L2924/053 (20130101); H01L2924/00014 (20130101)

Field of Classification Search

CPC: H01L (24/03); H01L (24/08); H01L (27/14636); H01L (27/1464); H01L (27/14645); H01L (27/14689); H01L (27/14621); H01L (27/14627); H10F (39/014); H10F (39/182); H10F (39/199); H10F (39/8053); H10F (39/8063); H10F (39/811)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9035445	12/2014	Lin et al.	N/A	N/A
9219032	12/2014	Ramachandran et al.	N/A	N/A
9679936	12/2016	Borthakur et al.	N/A	N/A
9741759	12/2016	Park	N/A	N/A
10270003	12/2018	Cheng	N/A	N/A
10991667	12/2020	Huang	N/A	H01L 24/03

11217547	12/2021	Chou	N/A	H01L 27/14621
11222915	12/2021	Hsu et al.	N/A	N/A
11694979	12/2022	Huang	257/734	H01L 27/14636
12341115	12/2024	Chou	N/A	H01L 24/03
2012/0062777	12/2011	Kobayashi	348/E5.091	H10F 39/18
2012/0068330	12/2011	Oganesian et al.	N/A	N/A
2012/0267745	12/2011	Tsuji	257/E31.127	H01L 27/14621
2013/0009270	12/2012	Tsai	257/E31.124	H10F 39/8057
2013/0032916	12/2012	Lin et al.	N/A	N/A
2013/0032920	12/2012	Lin et al.	N/A	N/A
2013/0037958	12/2012	Ho	257/E23.079	H10F 39/199
2013/0235243	12/2012	Sano	348/308	H10F 39/199
2013/0320475	12/2012	Takahashi	438/666	H10F 39/8053
2014/0008757	12/2013	Ramachandran	438/424	H01L 23/481
2014/0061839	12/2013	Ting	438/70	H10F 39/811
2014/0061842	12/2013	Ting	257/E31.124	H10F 39/026
2014/0094030	12/2013	Shimotsusa	438/652	H01L 21/76898
2015/0179693	12/2014	Maruyama et al.	N/A	N/A
2015/0243699	12/2014	Borthakur	348/307	H01L 27/14636
2015/0255495	12/2014	Park	N/A	N/A
2015/0318323	12/2014	Borthakur et al.	N/A	N/A
2016/0093661	12/2015	Hu	257/292	H10F 39/8053
2016/0300962	12/2015	Borthakur et al.	N/A	N/A
2016/0365378	12/2015	Chiang	N/A	H10F 19/904
2016/0379960	12/2015	Huang et al.	N/A	N/A
2017/0040358	12/2016	Kim	N/A	H10F 39/811
2017/0047301	12/2016	Yang et al.	N/A	N/A
2017/0141146	12/2016	Belsher	N/A	H10F 39/199
2017/0287878	12/2016	Huang et al.	N/A	N/A
2017/0301715	12/2016	Cheng et al.	N/A	N/A
2018/0114807	12/2017	Yamagishi	N/A	H10F 39/12
2018/0240833	12/2017	Tai et al.	N/A	N/A
2019/0088705	12/2018	Wang	N/A	H10F 39/026
2019/0148439	12/2018	Shin	257/443	H10F 19/50
2020/0373344	12/2019	Tung et al.	N/A	N/A
2021/0043593	12/2020	Huang	N/A	H01L 24/03

OTHER PUBLICATIONS

U.S. Appl. No. 16/558,556, filed Sep. 3, 2019. cited by applicant

Non-Final Office Action dated Aug. 31, 2020 for U.S. Appl. No. 16/532,781. cited by applicant

Notice of Allowance dated Dec. 24, 2020 for U.S. Appl. No. 16/532,781. cited by applicant

Non-Final Office Action dated Sep. 19, 2022 for U.S. Appl. No. 17/236,360. cited by applicant

Notice of Allowance dated Feb. 24, 2023 for U.S. Appl. No. 17/236,360. cited by applicant

Non-Final Office Action dated Dec. 2, 2024 for U.S. Appl. No. 18/660,276. cited by applicant

Notice of Allowance dated Jun. 4, 2025 for U.S. Appl. No. 18/660,276. cited by applicant

Primary Examiner: Hall; Victoria K.

Attorney, Agent or Firm: Eschweiler & Potashnik, LLC

Background/Summary

REFERENCE TO RELATED APPLICATIONS (1) This Application is a Continuation of U.S. application Ser. No. 17/236,360, filed on Apr. 21, 2021 (now U.S. Pat. No. 11,694,979, issued Jul. 4, 2023), which is a Continuation of U.S. application Ser. No. 16/532,781, filed on Aug. 6, 2019 (now U.S. Pat. No. 10,991,667, issued on Apr. 27, 2021). The contents of the above-referenced Patent Applications are hereby incorporated by reference in their entirety.

BACKGROUND

(1) Integrated circuits (ICs) with image sensors are used in a wide range of modern day electronic devices, such as cameras and cell phones, for example. Complementary metal-oxide semiconductor (CMOS) devices have become popular IC image sensors. Compared to charge-coupled devices (CCD), CMOS image sensors are increasingly favored due to low power consumption, small size, fast data processing, a direct output of data, and low manufacturing cost. Some types of CMOS image sensors include front-side illuminated (FSI) image sensors and back-side illuminated (BSI) image sensors.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIG. 1 illustrates a cross-sectional view of some embodiments of an integrated chip including a bond pad extending through a semiconductor substrate.
- (3) FIG. 2 illustrates a top view of some alternative embodiments of the IC of FIG. 1, as indicated by the cut-lines in FIGS. 1-2.
- (4) FIG. 3 illustrates a cross-sectional view of some embodiments of an image sensor including a bond pad laterally offset from a plurality of photodetectors.
- (5) FIG. 4 illustrates a top view of some alternative embodiments of the image sensor of FIG. 3, as indicated by the cut-lines in FIGS. 3-4.
- (6) FIGS. 5, 6A, 6B, 7, and 8 illustrate cross-sectional views of some alternative embodiments of a bond pad isolation structure surrounding a bond pad.
- (7) FIGS. 9-21 illustrate a series of cross-sectional views of some embodiments of a first method for forming a bond pad isolation structure surrounding a bond pad.
- (8) FIG. 22 illustrates a block diagram of some embodiments of the first method of FIGS. 9-21.
- (9) FIGS. 23-30 illustrate a series of cross-sectional views of some embodiments of a second method for forming a bond pad isolation structure surrounding a bond pad.
- (10) FIG. 31 illustrates a block diagram of some embodiments of the second method of FIGS. 23-30.
- (11) FIGS. 32-38 illustrates a series of cross-sectional views of some embodiments of a third method for forming a bond pad isolation structure surrounding a bond pad.
- (12) FIG. 39 illustrates a block diagram of some embodiments of the third method of FIGS. 32-38.

DETAILED DESCRIPTION

(13) The present disclosure provides many different embodiments, or examples, for implementing different features of this disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature

in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(14) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(15) Integrated chips typically comprise a plurality of metal interconnect layers arranged along a front-side of a substrate. The plurality of metal interconnect layers are configured to electrically connect devices (e.g., transistors, photodetectors, etc.) arranged within the substrate together. Back-side illuminated CMOS image sensors (BSI-CISs) comprise photodetectors arranged within the substrate in proximity to a back-side of the substrate, so that the photodetectors are able to receive light along the back-side of the substrate. By receiving light along the back-side of the substrate, incident light does not traverse the plurality of metal interconnect layers, thereby increasing an optical efficiency of the photodetectors.

(16) By virtue of the BSI-CISs receiving light along a back-side of a substrate, substrates having BSI-CIS are often placed within a packaging structure in a front-side down configuration that exposes the back-side of the substrate. Because the back-side of the substrate is exposed, bond pads are often arranged along the back-side of the substrate and are connected to metal interconnect layers. The bond pads may have a number of different configurations. For example, the bond pad may be disposed within a bond pad opening that extends through the front-side of the substrate to the back-side of the substrate. To electrically isolate the bond pad from the substrate, a dielectric structure is disposed along sidewalls of the substrate that define the bond pad opening. However, disposing the dielectric structure along the bond pad opening increases complexity, time, and cost associated with fabricating the BSI-CIS. Further, a top surface of the bond pad may be disposed below the back-side of the substrate. This may increase light received by the photodetectors; nevertheless this will decrease a reliability of a bond between the bond pad and another bonding structure. Furthermore, the bond pad may comprise an upper conductive segment extending over the back-side of the substrate, thereby increasing a reliability of the bond between the bond pad and another bonding structure. However, in such embodiments, the upper conductive segment may reflect light away from the photodetectors, thereby decreasing a reliability and/or a quality of images reproduced from the photodetectors.

(17) Accordingly, in some embodiments, the present disclosure relates to an integrated chip including a bond pad isolation structure surrounding a bond pad. The integrated chip includes a plurality of photodetectors arranged within a substrate. A bond pad region extends through the substrate, at a location laterally offset from the photodetectors, to a metal interconnect wire arranged within an interconnect dielectric structure disposed along a front-side of the substrate. The bond pad is disposed within the bond pad region and extends from the front-side of the substrate to a back-side of the substrate and is electrically coupled to the metal interconnect wire. In some embodiments, the bond pad directly contacts an upper surface of the substrate and contacts sidewalls of the substrate. The bond pad isolation structure has a ring-shape and laterally surrounds the bond pad. Further, the bond pad isolation structure extends from the back-side to the front-side of the substrate, thereby electrically isolating the bond pad from devices (e.g., the photodetectors and/or transistors) disposed on and/or within the substrate. The bond pad contacting the substrate

decreases complexity, time, and cost associated with forming the bond pad. Further, the bond pad isolation structure prevents “leakage” (i.e., a flow of current) from the bond pad to devices disposed on and/or within the substrate.

(18) FIG. 1 illustrates a cross-sectional view of some embodiments of an integrated chip **100** having a bond pad **116** disposed within a bond pad region **101b**.

(19) The integrated chip **100** includes an interconnect structure **104** disposed along a front-side **110fs** of a semiconductor substrate **110** (e.g., a silicon substrate). The interconnect structure **104** overlies a carrier substrate **102** (e.g., a silicon substrate), wherein the interconnect structure **104** is disposed between the semiconductor substrate **110** and the carrier substrate **102**. The interconnect structure **104** includes a plurality of interconnect layers arranged within an interconnect dielectric structure **103**. The plurality of interconnect layers alternate between conductive wires **108** and conductive vias **106**. The conductive wires **108** are configured to provide a lateral connection (i.e., a connection parallel to an upper surface of the carrier substrate **102**), whereas the conductive vias **106** are configured to provide for a vertical connection between adjacent conductive wires **108**. The conductive wires **108** include an upper conductive wire layer **108a**. A dielectric structure **118** overlies a back-side **110bs** of the semiconductor substrate **110**. A shallow trench isolation (STI) structure **112** is disposed within the semiconductor substrate **110** and extends along an upper surface of the interconnect dielectric structure **103**.

(20) The bond pad region **101b** extends through the semiconductor substrate **110**, at a location laterally offset from a device region **101a**, to the upper conductive wire layer **108a**. In some embodiments, the device region **101a** includes one or more semiconductor devices **120** (e.g., transistor(s), resistor(s), varactor(s), etc.) and/or photodetectors (not shown) disposed within and/or on the semiconductor substrate **110**. A bond pad **116** and a bond pad isolation structure **114** are disposed within the bond pad region **101b**. The bond pad **116** includes an upper conductive body **116a** and conductive protrusions **116b** underlying the upper conductive body **116a**. The upper conductive body **116a** comprises a same material (e.g., aluminum copper) as the conductive protrusions **116b**. In some embodiments, the upper conductive body **116a** directly overlies and directly contacts an upper surface **110us** of the semiconductor substrate **110**. In such embodiments, the conductive protrusions **116b** directly contact sidewalls of the semiconductor substrate **110** and extend from the upper conductive body **116a** to the upper conductive wire layer **108a**. Further, the upper conductive body **116a** has sidewalls that define pad openings **116o** overlying the conductive protrusions **116b**. The bond pad **116** may be configured to electrically couple the one or more semiconductor devices **120** to another integrated chip (not shown). In some embodiments, the upper conductive body **116a** is laterally offset from an inner sidewall **110is** of the semiconductor substrate **110** by a non-zero distance.

(21) A bond pad isolation structure **114** is laterally offset from and surrounds outer sidewalls of the bond pad **116**. In some embodiments, the bond pad isolation structure **114** comprises a material (e.g., silicon dioxide) different from the semiconductor substrate **110**. The bond pad isolation structure **114** may extend from the front-side **110fs** to the back-side **110bs** of the semiconductor substrate **110**. In some embodiments, the bond pad isolation structure **114** has a height $h_{sub.1}$ that is greater than or equal to a height $h_{sub.2}$ of the semiconductor substrate **110**. The bond pad isolation structure **114** is configured to electrically isolate the bond pad **116** from other devices (e.g., the semiconductor devices **120**) and/or doped regions (not shown) disposed within and/or on the semiconductor substrate **110**. This may mitigate and/or prevent a “leakage” (i.e., a flow of current) between the bond pad **116** and the other devices and/or doped regions disposed within and/or on the semiconductor substrate **110**, thereby increasing a reliability and endurance of the integrated chip **100**. Further, in some embodiments, when the bond pad **116** directly contacts the semiconductor substrate **110** complexity, cost, and time associated with forming the integrated chip **100** may be reduced.

(22) FIG. 2 illustrates a top view **200** of some alternative embodiments of the integrated chip **100**

of FIG. 1, as indicated by the cut-lines in FIGS. 1 and 2. For ease of illustration, the dielectric structure **118** of FIG. 1 has been omitted from the top view **200** of FIG. 2.

(23) As illustrated in FIG. 2, the bond pad isolation structure **114** has a ring like shape, where inner sidewalls of the bond pad isolation structure **114** completely surround outer sidewalls of the bond pad **116**. The inner sidewalls of the bond pad isolation structure **114** are laterally offset from outer sidewalls of the bond pad isolation structure **114** by a distance $d_{sub.1}$. In some embodiments, the distance $d_{sub.1}$ is non-zero. When viewed from above, the bond pad isolation structure **114** has a rectangular/square shape with rounded edges; however the bond pad isolation structure **114** may have other shapes, such as a circular/elliptical shape. When viewed from above, the bond pad **116** has a rectangular/square shape with rounded edges; however the bond pad **116** may have other shapes, such as a circular/elliptical shape. In some embodiments, a shape of the bond pad isolation structure **114** corresponds to a shape of the bond pad **116**. Further, the sidewalls of the bond pad **116** defining the pad openings **116o** are laterally offset from one another by a non-zero distance. In some embodiments, a solder bump (not shown) may be disposed laterally between the pad openings **116o**. When viewed from above, the pad openings **116o** may, for example, have a square/rectangular shape. The bond pad isolation structure **114** continuously wraps around the outer sidewalls of the bond pad **116** and extends from the front-side (**110fs** of FIG. 1) to the back-side (**110bs** of FIG. 1) of the semiconductor substrate **110**. Thus, the bond pad isolation structure **114** electrically isolates the bond pad **116** from other semiconductor devices and/or doped regions disposed within and/or on the semiconductor substrate **110**. The STI structure **112** directly underlies the bond pad **116**. In some embodiments, outer sidewalls of the bond pad **116** are laterally spaced between outer sidewalls of the STI structure **112**.

(24) FIG. 3 illustrates a cross-sectional view of some embodiments of an image sensor **300** including a bond pad **116** laterally offset from a plurality of photodetectors **302**.

(25) A semiconductor substrate **110** overlies a carrier substrate **102**. In some embodiments, the semiconductor substrate **110** and/or the carrier substrate **102** may respectively, for example, be a bulk substrate (e.g., a bulk silicon substrate), a silicon-on-insulator (SOI) substrate, or some other suitable substrate. The plurality of photodetectors **302** are disposed within the semiconductor substrate **110**. In some embodiments, the photodetectors **302** respectively extend from a back-side **110bs** of the semiconductor substrate **110** to a point below the back-side **110bs**. In further embodiments, the point is at a front-side **110fs** of the semiconductor substrate **110**, which is opposite the back-side **110bs** of the semiconductor substrate **110**. An interconnect structure **104** is disposed along the front-side **102fs** of the semiconductor substrate **110**. The interconnect structure **104** includes an interconnect dielectric structure **103**, a plurality of conductive wires **108**, and a plurality of conductive vias **106**. The semiconductor substrate **110** is bonded to the carrier substrate **102** by way of the interconnect structure **104**. In some embodiments, the conductive wires **108** and/or the conductive vias **106** may respectively, for example, be or comprise aluminum, copper, aluminum copper, tungsten, or the like. In some embodiments, the interconnect dielectric structure **103** may, for example, comprise one or more dielectric layers (e.g., silicon dioxide).

(26) A dielectric structure **118** overlies the back-side **110bs** of the semiconductor substrate **110**. In some embodiments, the dielectric structure **118** includes one or more dielectric layers, such as a first dielectric layer **304a**, a second dielectric layer **304b**, a third dielectric layer **304c**, and a fourth dielectric layer **304d**. In some embodiments, the first dielectric layer **304a** may, for example, be or comprise a metal oxide, such as aluminum oxide, or another suitable oxide. The second dielectric layer **304b** may, for example, be or comprise a metal oxide, such as hafnium oxide, or another suitable oxide. The third dielectric layer **304c** may, for example, be or comprise a metal oxide, such as tantalum oxide, or another suitable oxide. The fourth dielectric layer **304d** may, for example, be or comprise an oxide, such as silicon dioxide, another suitable oxide, undoped silicon glass (USG), polysilicon, another suitable dielectric and/or may have a thickness within a range of about 500 to 3,000 Angstroms. The dielectric structure **118** may be configured to protect the back-side **110bs** of

the semiconductor substrate **110**.

(27) An etch stop layer **306** overlies the dielectric structure **118**. A first grid layer **308** overlies the etch stop layer **306**, and a second grid layer **310** overlies the first grid layer **308**. A grid structure **312** includes a segment of the first and second grid layers **308**, **310** vertically above the photodetectors **302**. The grid structure **312** is laterally around and between the photodetectors **302** to define a plurality of color filter openings. A plurality of color filters **314** are arranged within the plurality of color filter openings and overlies the plurality of photodetectors **302**. The grid structure **312** comprises a dielectric material with a refractive index less than a refractive index of the color filters **314**. Due to the lower refractive index, the grid structure **312** serves as a radiation guide to direct incident electromagnetic radiation (i.e., light) to a corresponding photodetector **302**. Further, the color filters **314** are respectively configured to block a first range of frequencies of the incident electromagnetic radiation while passing a second range of frequencies (different than the first range of frequencies) of the incident electromagnetic radiation to an underlying photodetector **302**.

(28) In some embodiments, the etch stop layer **306** may, for example, be or comprise silicon carbide, silicon nitride, or the like and/or may have a thickness of about 1,500 Angstroms. In some embodiments, the first grid layer **308** may, for example, be or comprise an oxide, such as silicon dioxide, or another suitable oxide and/or may have a thickness of about 5,600 Angstroms. In further embodiments, the second grid layer **310** may, for example, be or comprise an oxide, such as silicon-oxy-nitride, or another suitable oxide and/or may have a thickness of about 1,500 Angstroms. In yet further embodiments, the first grid layer **308** may be or comprise a metal such as tungsten, another suitable metal, or the like. In such embodiments, the grid structure **312** may be configured as a composite grid structure comprising one or more metal layers and one or more dielectric layers. In further embodiments, the grid structure **312** may be configured as a dielectric grid structure comprising one or more dielectric layers.

(29) One or more semiconductor devices **120** (e.g., transistor(s), resistor(s), etc.) may be disposed within and/or on the front-side **110fs** of the semiconductor substrate. In such embodiments, the one or more semiconductor devices **120** may, for example, be pixel devices, such as a transfer transistor, a source follower transistor, a reset transistor, etc. The one or more semiconductor devices **120**, the photodetectors **302**, and the grid structure **312** are laterally arranged within a device region **101a** of the image sensor **300**. The device region **101a** is laterally offset from a bond pad region **101b** of the image sensor **300**. A bond pad **116** and a bond pad isolation structure **114** are laterally arranged within the bond pad region **101b** of the image sensor **300**. Thus, in some embodiments, the bond pad **116** and the bond pad isolation structure **114** are laterally offset from the photodetectors **302** and/or the one or more semiconductor devices **120** by a non-zero distance.

(30) The bond pad **116** is configured to electrically coupled the one or more semiconductor devices **120** and/or the photodetectors **302** to another integrated chip (not shown) by way of the interconnect structure **104**. In some embodiments, the bond pad **116** directly contacts an upper surface **110us** of the semiconductor substrate **110** and has protrusions extending through the semiconductor substrate **110** to the upper conductive wire layer **108a**. In such embodiments, the protrusions directly contact sidewalls of the semiconductor substrate **110** disposed below the upper surface **110us** of the semiconductor substrate **110**. The protrusions extend through a shallow trench isolation (STI) structure **112** and the interconnect dielectric structure **103**. Further, the bond pad **116** has sidewalls that define pad openings **116o** overlying the protrusions of the bond pad **116**. In further embodiments, the bond pad **116** is laterally offset upper sidewalls of the semiconductor substrate **110** and sidewalls of the dielectric structure **118** by a distance $d_{sub.2}$. In some embodiments, the distance $d_{sub.2}$ is non-zero, such that the bond pad **116** is may be electrically isolated from the dielectric structure **118**. Further, in such embodiments, by virtue of the non-zero distance $d_{sub.2}$, upper sidewalls of the semiconductor substrate **110** and/or sidewalls of the dielectric structure **118** may be protected from a bonding process performed on the bond pad **116** (i.e., from a downward force applied to the bond pad **116**). This may increase a structural integrity

of the image sensor **300**. In some embodiments, a top surface of the bond pad **116** is aligned with a top surface of the dielectric structure **118** (not shown) (e.g., see FIG. 5). The bond pad has a bond pad height h_{p1} defined from the upper surface **110_{us}** of the semiconductor substrate **110** to the top surface of the bond pad **116**. In some embodiments, the bond pad height h_{p1} is about 12,000 Angstroms.

(31) The bond pad isolation structure **114** laterally surrounds the bond pad **116**, wherein the bond pad isolation structure **114** extends from the back-side **110_{bs}** of the semiconductor to a point below the front-side **110_{fs}**. Thus, the bond pad isolation structure **114** electrically isolates the bond pad **116** from the one or more semiconductor device **120** and/or the photodetectors **302**, thereby preventing a “leakage” (i.e., a flow of current) between the bond pad **116** and the adjacent devices. This increases a performance, stability, and reliability of the image sensor **300**. The bond pad isolation structure **114** has a height h_{sub1} that is greater than a height h_{sub2} of the semiconductor substrate **110**. A bottom surface of the bond pad isolation structure **114** is vertically below the front-side **110_{fs}** of the semiconductor substrate **110** by a distance d_{subv} . In some embodiments, the distance d_{subv} is non-zero, wherein the bond pad isolation structure **114** extends into the interconnect dielectric structure **103**. In some embodiments, if the bottom surface of the bond pad isolation structure **114** is above the front-side **110_{fs}** (i.e., the distance d_{subv} is negative and/or the height h_{sub1} is less than the height h_{sub2}) then “leakage” may occur between the bond pad **116** and the one or more semiconductor devices **120** and/or the photodetectors **302**, thereby decreasing a performance of the image sensor **300**. The bond pad isolation structure **114** may, for example, be or comprise an oxide, such as silicon dioxide, or silicon nitride, silicon oxynitride, or the like.

(32) FIG. 4 illustrates a top view **400** of some alternative embodiments of the image sensor **300** of FIG. 3, as indicated by the cut-lines in FIGS. 3 and 4.

(33) As illustrated in FIG. 4, the bond pad isolation structure **114** has a ring like shape, where inner sidewalls of the bond pad isolation structure **114** completely surround outer sidewalls of the bond pad **116**. The outer sidewalls of the bond pad **116** are laterally offset from an inner sidewall **110_{is}** of the semiconductor substrate **110** by a distance d_{sub2} . In some embodiments, the distance d_{sub2} is non-zero. The color filters **314** are arranged in an array comprising rows and columns and respectively overlie the photodetectors (**302** of FIG. 3). In some embodiments, when viewed from above, the color filters **314** respectively have a rectangular/square shape and/or a circular/elliptical shape (not shown).

(34) FIG. 5 illustrates a cross-sectional view of some alternative embodiments of an integrated chip **500** having a bond pad **116** surrounded by a bond pad isolation structure **114**.

(35) A top surface **116_{ts}** of the bond pad **116** and a top surface of the dielectric structure **118** are respectively aligned along a substantially straight line **502**. In some embodiments, the substantially straight line **502** is parallel to the back-side **110_{bs}** of the semiconductor substrate **110**. In further embodiments, the top surface **116_{ts}** of the bond pad **116** is above the top surface of the dielectric structure **118** (not shown). Further, the bond pad isolation structure **114** has slanted sidewalls, wherein a width W_{sub1} of the bond pad isolation structure **114** continuously increases from the back-side **110_{bs}** of the semiconductor substrate **110** to the front-side **110_{fs}** of the semiconductor substrate **110**. In such embodiments, during a formation of the integrated chip **500**, the bond pad isolation structure **114** may, for example, have been formed concurrently with the STI structure **112**, or after forming the STI structure **112** and before forming the interconnect structure **104**. In some embodiments, for example, the substantially straight line **502** is configured as a level horizontal line. In further embodiments, the substantially straight line **502** may vary within a range of -25 to 25 Angstroms or within a range of -5 to 5 Angstroms from a level horizontal line disposed along the top surface **116_{ts}** of the bond pad **116**. In yet further embodiments, an angle is defined between a first point disposed along the substantially straight line **502** and a second point disposed along the substantially straight line **502**, where the first point is laterally offset from the

second point, and the angle is about 180 degrees.

(36) FIG. 6A illustrates a cross-sectional view of some alternative embodiments of an integrated chip **600** having a bond pad **116** surrounded by a bond pad isolation structure **114**.

(37) The bond pad isolation structure **114** extends from the back-side **110bs** of the semiconductor substrate **110** to a point below the front-side **110fs** of the semiconductor substrate **110**. In some embodiments, a bottom surface of the bond pad isolation structure **114** may be aligned with the front-side **110fs** of the semiconductor substrate **110** (not shown). The bond pad isolation structure **114** has slanted sidewalls, wherein a width $W_{sub.1}$ of the bond pad isolation structure **114** continuously decreases from the back-side **110bs** of the semiconductor substrate **110** to the front-side **110fs** of the semiconductor substrate **110**. In such embodiments, during a formation of the integrated chip **600**, the bond pad isolation structure **114** may, for example, have been formed after forming the interconnect structure **104**.

(38) FIG. 6B illustrates a cross-sectional view of some alternative embodiments of the integrated chip **600** of FIG. 6A, where the bond pad isolation structure **114** is spaced laterally between outer sidewalls of the STI structure **112**.

(39) FIG. 7 illustrates a cross-sectional view of some alternative embodiments of an integrated chip **700** having a device region **101a** laterally offset from a bond pad region **101b**.

(40) A device STI structure **702** is disposed within the device region **101a**, wherein the device STI structure **702** comprises a same material as the STI structure **112**. In some embodiments, the device STI structure **702** has a bottom surface and a top surface that are respectively aligned with a bottom surface and a top surface of the STI structure **112**. In further embodiments, the device STI structure **702** has a ring-shape and surrounds at least one semiconductor device **120** disposed within and/or on the semiconductor substrate **110**. The device STI structure **702** may further increase an electrical isolation between the semiconductor device **120** and the bond pad **116**. Further, a bottom surface of the bond pad isolation structure **114** is aligned with the bottom surface of the STI structure **112** and/or the bottom surface of the device STI structure **702**. In some embodiments, the STI structure **112** continuously extends between outer sidewalls of the bond pad isolation structure **114**, wherein the STI structure **112** further increases electrical isolation between the bond pad **116** and other devices disposed on and/or within the semiconductor substrate **110** (e.g. the semiconductor device **120**, photodetectors (not shown), etc.). In further embodiments, the STI structure **112** and the bond pad isolation structure **114** comprise a same material, wherein the bond pad isolation structure **114** is a protrusion of the STI structure **112**.

(41) FIG. 8 illustrates a cross-sectional view of some alternative embodiments of an integrated chip **800** having a bond pad isolation structure **114** disposed around a bond pad **116**.

(42) A first insulator layer **802** is disposed along sidewalls of the dielectric structure **118** and sidewalls of the semiconductor substrate **110**. The first insulator layer **802** is disposed between the bond pad **116** and the upper surface **110us** of the semiconductor substrate **110**. The bond pad **116** includes a conductive body disposed above the upper surface **110us** of the semiconductor substrate **110**, and conductive protrusions extending from the conductive body to the upper conductive wire layer **108a**. A second insulator layer **804** is disposed along sidewalls of the first insulator layer **802** and along sidewalls of the protrusions of the bond pad **116**. The second insulator layer **804** is disposed between sidewalls of the semiconductor substrate **110** and the protrusions of the bond pad **116**, wherein the second insulator layer **804** continuously extends around the respective protrusions. The first and second insulator layers **802**, **804** are respectively configured to electrically isolate the bond pad **116** from the semiconductor substrate **110**. This further increases a performance and reliability of the integrated chip **800**. In some embodiments, the first insulator layer **802** may, for example, be or comprise an oxide, such as silicon dioxide, undoped silicon glass silicon dioxide (USGOX), another suitable oxide, or the like. In some embodiments, the second insulator layer **804** may, for example, be or comprise an oxide, such as silicon dioxide, USGOX, another suitable oxide, or the like.

(43) FIGS. **9-21** illustrate cross-sectional views **900-2100** of some embodiments of a first method of forming an integrated chip including a bond pad isolation structure surrounding a bond pad according to aspects of the present disclosure. Although the cross-sectional views **900-2100** shown in FIGS. **9-21** are described with reference to a first method, it will be appreciated that the structures shown in FIGS. **9-21** are not limited to the method but rather may stand alone separate of the method. Although FIGS. **9-21** are described as a series of acts, it will be appreciated that these acts are not limiting in that the order of the acts can be altered in other embodiments, and the methods disclosed are also applicable to other structures. In other embodiments, some acts that are illustrated and/or described may be omitted in whole or in part.

(44) As shown in cross-sectional view **900** of FIG. **9**, a semiconductor substrate **110** is provided and a masking layer **902** is formed on a front-side **110fs** of the semiconductor substrate **110**. In some embodiments, the semiconductor substrate **110** may, for example, be a bulk substrate (e.g., a bulk silicon substrate), a silicon-on-insulator (SOI) substrate, or some other suitable substrate. A shallow trench isolation (STI) structure **112** is formed on the front-side **110fs** of the semiconductor substrate **110**. In some embodiments, a process for forming the STI structure **112** may include: selectively etching the semiconductor substrate **110** to form a trench that extends into the front-side **110fs** of the semiconductor substrate **110**; and filling (e.g., by chemical vapor deposition (CVD), physical vapor deposition (PVD), atomic layer deposition (ALD), thermal oxidation, etc.) the trench with a dielectric material (e.g., silicon dioxide, silicon carbide, etc.). In further embodiments, the semiconductor substrate **110** is selectively etched by exposing unmasked portions of the semiconductor substrate **110** to one or more etchants configured to selectively remove unmasked portions of the semiconductor substrate **110**. The masking layer **902** may, for example, be or comprise silicon-oxy-nitride.

(45) As shown in cross-sectional view **1000** of FIG. **10**, a deep trench isolation (DTI) layer **1002** is formed over and into the semiconductor substrate **110**. In some embodiments, a process for forming the DTI layer **1002** includes: forming a second masking layer over the masking layer **902** and the STI structure **112**; patterning the semiconductor substrate **110** and the masking layer **902** according to the second masking layer, thereby forming DTI openings in the semiconductor substrate **110**; forming (e.g., by a plasma-enhanced CVD (PECVD) process, a high aspect ratio process (HARP), PVD, or another suitable deposition process) a DTI material (e.g., silicon oxide, silicon nitride, silicon oxynitride, plasma-enhanced oxide (PEOX), another suitable dielectric material, or the like) over the semiconductor substrate **110**, wherein the DTI material fills the DTI openings. In some embodiments, forming the DTI material includes forming a first dielectric layer (e.g., comprising silicon oxide) over a second dielectric layer (e.g., comprising silicon nitride), the second dielectric layer lines the DTI openings and the first dielectric layer fills a remaining portion of the DTI openings. In some embodiments, a bottom surface of the DTI layer **1002** is disposed above a back-side **110bs** of the semiconductor substrate **110**. In some embodiments, the DTI layer **1002** is formed by, for example, CVD, PVD, ALD, or another suitable deposition process. In some embodiments, the DTI layer **1002** has a height $h_{sub.1}$ within a range of about 12,000 to 15,000 Angstroms or greater than 20,000 Angstroms.

(46) As shown in cross-sectional view **1100** of FIG. **11**, a planarization process is performed on the DTI layer (**1002**, FIG. **10**), thereby defining a bond pad isolation structure **114**. In some embodiments, the planarization process includes performing a chemical-mechanical planarization (CMP) on the DTI layer (**1002**, FIG. **10**) and/or the STI structure **112** until the front-side **110fs** of the semiconductor substrate **110** is reached. In further embodiments, the planarization process may remove the masking layer **902**. In some embodiments, after performing the planarization process the bond pad isolation structure **114** has a height $h_{sub.1}$ that is greater than 2 micrometers. In further embodiments, a width $W_{sub.1}$ of the bond pad isolation structure **114** continuously decreases from the front-side **110fs** to a point above the back-side **110bs** of the semiconductor substrate **110**.

(47) In some embodiments, the planarization process includes performing a CMP on the DTI layer **1002**, FIG. **10**) until a top surface of the STI structure **112** is exposed, thereby defining the bond pad isolation structure **114** (not shown). In such embodiments, an upper surface of the STI structure **112** and an upper surface of the bond pad isolation structure **114** are respectively vertically offset from the front-side **110fs** of the semiconductor substrate **110**, as illustrated in the cross-sectional view of FIG. **7**. Further, in such embodiments, after performing the planarization a removal process is performed to remove the masking layer **902** (not shown).

(48) As shown in cross-sectional view **1200** of FIG. **12**, an interconnect structure **104** is formed on the front-side **110fs** of the semiconductor substrate **110**. The interconnect structure **104** includes an interconnect dielectric structure **103**, a plurality of conductive wires **108**, and a plurality of conductive vias **106**. In some embodiments, the interconnect dielectric structure **103** may be or comprise one or more inter-level dielectric (ILD) layers. The one or more ILD layers may, for example, be or comprise an oxide, such as silicon dioxide, or another suitable oxide. In some embodiments, a process for forming the interconnect structure **104** includes forming the conductive vias **106** and the conductive wires **108** by a single damascene process or a dual damascene process. For example, a first layer of the conductive vias **106** and a first layer of the conductive wires **108** may respectively be formed by a single damascene process. Further, in such embodiments, the process includes forming remaining layers of the conductive wires **108** and the conductive vias **106** by repeatedly performing a dual damascene process. In some embodiments, the conductive wires **108** and/or the conductive vias **106** may respectively, for example, be or comprise aluminum, copper, aluminum copper, tungsten, or the like.

(49) As shown in cross-sectional view **1300** of FIG. **13**, the structure of FIG. **12** is rotated 180 degrees and the interconnect structure **104** is bonded to a carrier substrate **102**. In some embodiments, the bonding process may comprise a fusion bonding process. In some embodiments, the carrier substrate **102** may, for example, be a bulk substrate (e.g., a bulk silicon substrate), a silicon-on-insulator (SOI) substrate, or some other suitable substrate. In some embodiments, after performing the bonding process, a thinning process is performed on the semiconductor substrate **110** until the bond pad isolation structure **114** is exposed. In such embodiments, the thinning process reduces an initial thickness $T_{sub.i}$ of the semiconductor substrate to a thickness $T_{sub.s}$. In some embodiments, the thickness $T_{sub.s}$ is equal to the height $h_{sub.1}$ of the bond pad isolation structure **114**. In further embodiments, the thinning process is performed by a mechanical grinding process, a CMP, some other thinning process, or any combination of the foregoing. For example, the thinning process may be performed wholly by a mechanical grinding process.

(50) As shown in cross-sectional view **1400** of FIG. **14**, a dielectric structure **118** is formed over the back-side **110bs** of the semiconductor substrate **110**. In some embodiments, the dielectric structure **118** includes one or more dielectric layers, such as a first dielectric layer **304a**, a second dielectric layer **304b**, a third dielectric layer **304c**, and a fourth dielectric layer **304d**. In some embodiments, the first dielectric layer **304a**, the second dielectric layer **304b**, the third dielectric layer **304c** and/or the fourth dielectric layer **304d** may respectively be formed by CVD, PVD, ALD, or another suitable deposition process. In further embodiments, the first, second, third, and fourth dielectric layers **304a-d** may respectively comprise a dielectric material different from one another. For example, the first dielectric layer **304a** may comprise aluminum oxide, the second dielectric layer **304b** may comprise hafnium oxide, the third dielectric layer **304c** may comprise tantalum oxide, and the fourth dielectric layer **304d** may comprise silicon dioxide. The fourth dielectric layer **304d** may, for example, have a thickness of about 1,300 Angstroms. Further, a dielectric protection layer **1202** is formed over the dielectric structure **118**. The dielectric protection layer **1202** may comprise an oxide (such as silicon dioxide) and/or may act as a hard mask protection layer for the dielectric structure **118** during subsequent processing steps. In some embodiments, the dielectric protection layer **1202** may, for example, have a thickness of about 4,500 Angstroms. In such embodiments, the thickness of the dielectric protection layer **1202** is sufficiently large (e.g., about 4,500 Angstroms),

such that a thickness of the fourth dielectric layer is not reduced during subsequent processing steps (e.g., the first etch process of FIG. 15 and/or the second etch process of FIG. 16). In some embodiments, the dielectric structure **118** has a thickness $t_{sub.1}$ of about 2,000 Angstroms.

(51) As shown in cross-sectional view **1500** of FIG. 15, a first etch process is performed on the dielectric protection layer **1202**, the dielectric structure **118**, and the semiconductor substrate **110**, thereby forming plug openings **1302**. In some embodiments, the first etch process may include performing a wet etch process, a dry etch process, or another suitable etch process. In some embodiments, the first etch process includes: forming a masking layer (not shown) over the dielectric protection layer **1202**; exposing unmasked regions of the dielectric protection layer **1202** and underlying layers to one or more etchants, thereby defining the plug openings **1302**; and performing a removal process to remove the masking layer.

(52) As shown in cross-sectional view **1600** of FIG. 16, a second etch process is performed on the STI structure **112**, the interconnect dielectric structure **103**, and the dielectric protection layer (**1202**). This expands the plug openings **1302** and exposes an upper surface of an upper conductive wire layer **108a**. In some embodiments, the second etch process may include performing a wet etch process, a dry etch process, or another suitable etch process. In some embodiments, the second etch process may include performing a blanket dry etch process on the structure of FIG. 15. In such embodiments, the dielectric protection layer (**1202**) may be removed by the blanket dry etch process and/or the thickness of the fourth dielectric layer **304d** may, for example, be about 1,300 Angstroms after performing the second etch process.

(53) As shown in cross-sectional view **1700** of FIG. 17, plug structures **1702** are formed within at least a portion of the plug openings **1302**. In some embodiments, an upper surface of the plug structures **1702** is disposed below the back-side **110bs** of the semiconductor substrate **110**. In some embodiments, a process for forming the plug structures **1702** includes: forming a plug material within the plug openings **1302**; and performing an etch back process (e.g., a dry etch process, a wet etch process, etc.) to remove at least a portion of the plug material, thereby defining the plug structures **1702**.

(54) As shown in cross-sectional view **1800** of FIG. 18, a third etch process is performed on the dielectric structure **118** and the semiconductor substrate **110**, thereby defining a bond pad opening **1802**. The third etch process defines an upper surface **110us** of the semiconductor substrate **110**, wherein the upper surface **110us** of the semiconductor substrate **110** is below the upper surface of the plug structures **1702**. In some embodiments, the third etch process may include performing a wet etch process, a dry etch process, or another suitable etch process. In some embodiments, the third etch process includes: forming a masking layer (not shown) over the dielectric structure **118**; exposing unmasked regions of the dielectric structure **118** and the semiconductor substrate **110** to one or more etchants, thereby defining the bond pad opening **1802**; and performing a removal process to remove the masking layer.

(55) As shown in cross-sectional view **1900** of FIG. 19, a plug removal process is performed to remove the plug structures **1702**, thereby expanding the bond pad opening **1802** and exposing the upper surface of the upper conductive wire layer **108a**. In some embodiments, the plug removal process includes performing a wet ash process and/or a dry ash process, then performing a wet etch process.

(56) As shown in cross-sectional view **2000** of FIG. 20, a bond pad layer **2002** is formed over the structure of FIG. 19. In some embodiments, the bond pad layer **2002** may, for example, be deposited and/or grown by electroless plating, electroplating, sputtering, or another suitable deposition process. In further embodiments, the bond pad layer **2002** may, for example, be or comprise aluminum, copper, aluminum copper, or the like. In some embodiments, the bond pad layer **2002** may comprise a same material as the conductive vias **106** and/or the conductive wires **108**.

(57) As shown in cross-sectional view **2100** of FIG. 21, a fourth etch process is performed on the

bond pad layer (**2002** of FIG. **20**), thereby defining a bond pad **116**. The bond pad **116** is laterally offset from sidewalls of the semiconductor substrate **110** and the dielectric structure **118** by a distance $d_{sub.2}$. In some embodiments, the distance $d_{sub.2}$ is non-zero. In further embodiments, the fourth etch process includes: forming a masking layer (not shown) over the bond pad layer (**2002** of FIG. **20**); exposing unmasked regions of the bond pad layer (**2002** of FIG. **20**) to one or more etchants, thereby defining the bond pad **116**; and performing a removal process to remove the masking layer.

(58) Although FIGS. **9-13** describe forming the bond pad isolation structure **114** before forming the interconnect structure **104** on the front-side **110f**s of the semiconductor substrate **110**, it will be appreciated that formation of the bond pad isolation structure **114** is not limited to such fabrication methods. For example, in some embodiments, the bond pad isolation structure **114** may be formed after forming the interconnect structure **104**, wherein the bond pad isolation structure **114** extends into an upper surface of the interconnect dielectric structure **103** (e.g., see the integrated chip **600** of FIG. **6A**). In such embodiments, the bond pad isolation structure **114** may, for example, be formed after the thinning process of FIG. **13** but before formation of the dielectric structure **118**. In yet further embodiments, the bond pad isolation structure **114** may, for example, be formed after forming the bond pad **116**. In such embodiments, the bond pad isolation structure **114** extends through the dielectric structure **118** to the front-side **110f**s of the semiconductor substrate **110** (not shown).

(59) FIG. **22** illustrates a first method **2200** of forming an integrated circuit according to the present disclosure. Although the first method **2200** is illustrated and/or described as a series of acts or events, it will be appreciated that the method is not limited to the illustrated ordering or acts. Thus, in some embodiments, the acts may be carried out in different orders than illustrated, and/or may be carried out concurrently. Further, in some embodiments, the illustrated acts or events may be subdivided into multiple acts or events, which may be carried out at separate times or concurrently with other acts or sub-acts. In some embodiments, some illustrated acts or events may be omitted, and other un-illustrated acts or events may be included.

(60) At act **2202**, a shallow trench isolation (STI) structure is formed on a front-side of a semiconductor substrate. FIG. **9** illustrates a cross-sectional view **900** corresponding to some embodiments of act **2202**.

(61) At act **2204**, a bond pad isolation structure is formed in the semiconductor substrate. The bond pad isolation structure extends from the front-side of the semiconductor substrate to a back-side of the semiconductor substrate. FIGS. **10** and **11** illustrate cross-sectional views **1000** and **1100** corresponding to some embodiments of act **2204**.

(62) At act **2206**, an interconnect structure is formed on the front-side of the semiconductor substrate. The interconnect structure includes an upper conductive wire layer. FIG. **12** illustrates a cross-sectional view **1200** corresponding to some embodiments of act **2206**.

(63) At act **2208**, a dielectric structure is formed over the back-side of the semiconductor substrate. FIG. **14** illustrates a cross-sectional view **1400** corresponding to some embodiments of act **2208**.

(64) At act **2210**, an etch process is performed to define plug openings in the semiconductor substrate, thereby exposing an upper surface of the upper conductive wire layer. FIGS. **15** and **16** illustrate cross-sectional views **1500** and **1600** corresponding to some embodiments of act **2210**.

(65) At act **2212**, plugs are formed in the plug openings. An upper surface of the plugs is disposed between the front-side and the back-side of the semiconductor substrate. FIG. **17** illustrates a cross-sectional view **1700** corresponding to some embodiments of act **2212**.

(66) At act **2214**, the dielectric structure and the semiconductor substrate are patterned, thereby defining a bond pad opening and an upper surface of the semiconductor substrate. FIG. **18** illustrates a cross-sectional view **1800** corresponding to some embodiments of act **2214**.

(67) At act **2216**, the plugs are removed, thereby expanding the bond pad opening and exposing the upper surface of the upper conductive wire layer. FIG. **19** illustrates a cross-sectional view **1900**

corresponding to some embodiments of act **2216**.

(68) At act **2218**, a bond pad is formed in the bond pad openings. The bond pad isolation structure continuously extends around the bond pad. FIGS. **20** and **21** illustrate cross-sectional views **2000** and **2100** corresponding to some embodiments of act **2218**.

(69) FIGS. **23-30** illustrate cross-sectional views **2300-3000** of some embodiments of a second method of forming an integrated chip including a bond pad isolation structure surrounding a bond pad according to aspects of the present disclosure. Although the cross-sectional views **2300-3000** shown in FIGS. **23-30** are described with reference to a second method, it will be appreciated that the structures shown in FIGS. **23-30** are not limited to the method but rather may stand alone separate of the method. Although FIGS. **23-30** are described as a series of acts, it will be appreciated that these acts are not limiting in that the order of the acts can be altered in other embodiments, and the methods disclosed are also applicable to other structures. In other embodiments, some acts that are illustrated and/or described may be omitted in whole or in part.

(70) As shown in cross-sectional view **2300** of FIG. **23**, the dielectric structure **118** is formed over the semiconductor substrate **110**. In some embodiments, the structure of FIG. **23** is formed as illustrated and/or described in FIGS. **9-14**.

(71) As shown in cross-sectional view **2400** of FIG. **24**, a first etch process is performed on the dielectric structure **118** and the semiconductor substrate **110**, thereby forming a bond pad opening **2402**. In some embodiments, the first etch process may, for example, be or comprise a dry etch process, a wet etch process, or another suitable etch process. In some embodiments, the first etch process includes: forming a masking layer (not shown) over the dielectric structure **118**; exposing unmasked regions of the dielectric structure **118** and the semiconductor substrate **110** to one or more etchants, thereby defining the bond pad opening **2402**; and performing a removal process to remove the masking layer. In some embodiments, the first etch process defines an upper surface **110us** of the semiconductor substrate **110** disposed below the back-side **110bs** of the semiconductor substrate **110**.

(72) As shown in cross-sectional view **2500** of FIG. **25**, a first insulator layer **802** is formed over the dielectric structure **118** and the semiconductor substrate **110**, wherein the first insulator layer **802** lines at least a portion of the bond pad opening **2402**. In some embodiments, the first insulator layer **802** may, for example, be or comprise an oxide, such as silicon oxide, or another suitable oxide and/or has a thickness of about 4,500 Angstroms. In further embodiments, the thickness of the first insulator layer **802** is sufficiently large (e.g., about 4,500 Angstroms), such that a thickness of the fourth dielectric layer **304d** is not reduced during subsequent processing steps (e.g., the third etch process of FIG. **28**).

(73) As shown in cross-sectional view **2600** of FIG. **26**, a second etch process is performed on the first insulator layer **802** and the semiconductor substrate **110**, thereby expanding the bond pad opening **2402** and exposing an upper surface of the STI structure **112**. In some embodiments, the second etch process includes: forming a masking layer (not shown) over the first insulator layer **802**; exposing unmasked regions of the first insulator layer **802** and the semiconductor substrate **110** to one or more etchants, thereby exposing the upper surface of the STI structure **112**; and performing a removal process to remove the masking layer.

(74) As shown in cross-sectional view **2700** of FIG. **27**, a second insulator layer **804** is formed over the first insulator layer **802** and the semiconductor substrate **110**. The second insulator layer **804** lines the bond pad opening **2402**. In some embodiments, the second insulator layer **804** may, for example, be formed by PVD, CVD, or another suitable deposition process. In some embodiments, the second insulator layer **804** may, for example, be or comprise an oxide, such as silicon oxide, or another suitable oxide.

(75) As shown in cross-sectional view **2800** of FIG. **28**, a third etch process is performed on the first and second insulator layers **802**, **804**, the STI structure **112**, and the interconnect dielectric structure **103**, thereby exposing an upper surface of the upper conductive wire layer **108a**. In some

embodiments, the third etch process may include performing a wet etch process, a dry etch process, or another suitable etch process. In further embodiments, the third etch process may include performing a blanket dry etch process on the structure of FIG. 27, thereby removing the first insulator layer **802** from an upper surface of the fourth dielectric layer **304d**. In such embodiments, a thickness of the fourth dielectric layer **304d** after the third etch process may be about 1,300 Angstroms.

(76) As shown in cross-sectional view **2900** of FIG. 29, a bond pad layer **2002** is formed in the bond pad opening **2402**. In some embodiments, the bond pad layer **2002** may, for example, be deposited and/or grown by electroless plating, electroplating, sputtering, or another suitable deposition process. In further embodiments, the bond pad layer **2002** may, for example, be or comprise aluminum, copper, aluminum copper, or the like. In further embodiments, the bond pad layer **2002** may comprise a same material as the conductive vias **106** and/or the conductive wires **108**.

(77) As shown in cross-sectional view **3000** of FIG. 30, a fourth etch process is performed on the bond pad layer (**2002** of FIG. 29), thereby defining a bond pad **116**. The bond pad **116** is laterally offset from sidewalls of the first and second insulator layers **802**, **804** by a distance $d_{sub.2}$. In some embodiments, the distance $d_{sub.2}$ is non-zero. In further embodiments, the fourth etch process includes: forming a masking layer (not shown) over the bond pad layer (**2002** of FIG. 29); exposing unmasked regions of the bond pad layer (**2002** of FIG. 29) to one or more etchants, thereby defining the bond pad **116**; and performing a removal process to remove the masking layer.

(78) FIG. 31 illustrates a second method **3100** of forming an integrated circuit according to the present disclosure. Although the second method **3100** is illustrated and/or described as a series of acts or events, it will be appreciated that the method is not limited to the illustrated ordering or acts. Thus, in some embodiments, the acts may be carried out in different orders than illustrated, and/or may be carried out concurrently. Further, in some embodiments, the illustrated acts or events may be subdivided into multiple acts or events, which may be carried out at separate times or concurrently with other acts or sub-acts. In some embodiments, some illustrated acts or events may be omitted, and other un-illustrated acts or events may be included.

(79) At act **3102**, a shallow trench isolation (STI) structure is formed on a front-side of a semiconductor substrate. FIG. 9 illustrates a cross-sectional view **900** corresponding to some embodiments of act **3102**.

(80) At act **3104**, a bond pad isolation structure is formed in the semiconductor substrate. The bond pad isolation structure extends from the front-side of the semiconductor substrate to a back-side of the semiconductor substrate. FIGS. 10 and 11 illustrate cross-sectional views **1000** and **1100** corresponding to some embodiments of act **3104**.

(81) At act **3106**, an interconnect structure is formed on the front-side of the semiconductor substrate. The interconnect structure includes an upper conductive wire layer. FIG. 12 illustrates a cross-sectional view **1200** corresponding to some embodiments of act **3106**.

(82) At act **3108**, a dielectric structure is formed over the back-side of the semiconductor substrate. FIG. 14 illustrates a cross-sectional view **1400** corresponding to some embodiments of act **3108**.

(83) At act **3110**, the dielectric structure and the semiconductor substrate are patterned, thereby defining a bond pad opening. FIG. 24 illustrates a cross-sectional view **2400** corresponding to some embodiments of act **3110**.

(84) At act **3112**, a first insulator layer is formed over the dielectric structure and the semiconductor substrate. The first insulator layer lines the bond pad opening. FIG. 25 illustrates a cross-sectional view **2500** corresponding to some embodiments of act **3112**.

(85) At act **3114**, the first insulator layer and the semiconductor substrate are patterned, thereby expanding the bond pad opening and exposing an upper surface of the STI structure. FIG. 26 illustrates a cross-sectional view **2600** corresponding to some embodiments of act **3114**.

(86) At act **3116**, a second insulator layer is formed over the first insulator layer and the STI

structure. FIG. 27 illustrates a cross-sectional view 2700 corresponding to some embodiments of act 3116.

(87) At act 3118, the first and second insulator layers, the STI structure, and the interconnect structure are patterned, thereby exposing an upper surface of the upper conductive wire layer and expanding the bond pad opening. FIG. 28 illustrates a cross-sectional view 2800 corresponding to some embodiments of act 3118.

(88) At act 3120, a bond pad is formed in the bond pad opening. The bond pad isolation structure continuously extends around the bond pad. FIGS. 29 and 30 illustrate cross-sectional views 2900 and 3000 corresponding to some embodiments of act 3120.

(89) FIGS. 32-38 illustrate cross-sectional views 3200-3800 of some embodiments of a third method of forming an integrated chip including a bond pad isolation structure surrounding a bond pad according to aspects of the present disclosure. Although the cross-sectional views 3200-3800 shown in FIGS. 32-38 are described with reference to a third method, it will be appreciated that the structures shown in FIGS. 32-38 are not limited to the method but rather may stand alone separate of the method. Although FIGS. 32-38 are described as a series of acts, it will be appreciated that these acts are not limiting in that the order of the acts can be altered in other embodiments, and the methods disclosed are also applicable to other structures. In other embodiments, some acts that are illustrated and/or described may be omitted in whole or in part.

(90) As shown in cross-sectional view 3200 of FIG. 32, the shallow trench isolation (STI) structure 112 is formed on the front-side 110fs of the semiconductor substrate 110. In some embodiments, the STI structure 112 of FIG. 32 is formed as illustrated and/or described in FIGS. 9-11.

(91) As shown in cross-sectional view 3300 of FIG. 33, an interconnect structure 104 is formed on the front-side 110fs of the semiconductor substrate 110. The interconnect structure 104 is bonded to a carrier substrate 102, and a dielectric structure 118 is formed over the back-side 110bs of the semiconductor substrate 110. Further, a dielectric protection layer 1202 is formed over the dielectric structure 118. In some embodiments, the structure of FIG. 33 is formed as illustrated and/or described in FIGS. 12-14.

(92) As shown in cross-sectional view 3400 of FIG. 34, an etch process is performed on the dielectric protection layer 1202, the dielectric structure 118, and the semiconductor substrate 110, thereby forming bond pad isolation openings 3402. In some embodiments, the etch process may remove at least a portion of the interconnect dielectric structure 103. In some embodiments, the etch process may include performing a wet etch process, a dry etch process, or another suitable etch process. In some embodiments, the etch process includes: forming a masking layer (not shown) over the dielectric protection layer 1202; exposing unmasked regions of the dielectric protection layer 1202 and underlying layers to one or more etchants, thereby defining the bond pad isolation openings 3402; and performing a removal process to remove the masking layer.

(93) As shown in cross-sectional view 3500 of FIG. 35, a first DTI layer 3502 and a second DTI layer 3504 are formed over the dielectric protection layer 1202 and within the bond pad isolation openings (3402 of FIG. 34). In some embodiments, the first DTI layer 3502 is omitted and the second DTI layer 3504 completely fills the bond pad isolation openings (3402 of FIG. 34). In some embodiments, the first DTI layer 3502 may, for example, be or comprise an oxide, such as silicon dioxide, another suitable oxide, or the like and/or may be formed to a thickness of about 15,000 Angstroms. In further embodiments, the second DTI layer 3504 may, for example, be or comprise silicon oxynitride, another suitable dielectric material, or the like and/or may be formed to a thickness of about 700 Angstroms.

(94) As shown in cross-sectional view 3600 of FIG. 36, a planarization process is performed on the first and/or second DTI layers (3502, 3504 of FIG. 35) thereby defining a bond pad isolation structure 114. The bond pad isolation structure 114 may comprise a first bond pad isolation layer 114a and/or a second bond pad isolation layer 114b. In some embodiments, the planarization process includes performing a chemical-mechanical planarization (CMP) on the first and second

DTI layers (**3502**, **3504** of FIG. **35**) and the dielectric protection layer **1202**. In further embodiments, the planarization process may reduce a thickness of the dielectric protection layer **1202**.

(95) As shown in cross-sectional view **3700** of FIG. **37**, a bond pad **116** is formed in the semiconductor substrate **110** and is continuously surrounded by the bond pad isolation structure **114**. In some embodiments, the structure of FIG. **37** is formed as illustrated and/or described in FIGS. **15-21**. In further embodiments, the bond pad **116** is formed as illustrated and/or described in FIGS. **24-30**. The structure of FIG. **37** may be formed by omitting the first DTI layer (**3502** of FIG. **35**), in which the bond pad isolation structure **114** comprises the first bond pad isolation layer **114a**. In some embodiments, the first bond pad isolation layer **114a** may, for example, be or comprise silicon dioxide, another suitable oxide, or the like.

(96) As shown in cross-sectional view **3800** of FIG. **38**, a bond pad **116** is formed in the semiconductor substrate **110** and is continuously surrounded by the bond pad isolation structure **114**. In some embodiments, the structure of FIG. **38** is formed as illustrated and/or described in FIGS. **15-21**. In further embodiments, the bond pad **116** is formed as illustrated and/or described in FIGS. **24-30**. The bond pad isolation structure **114** comprises the first bond pad isolation layer **114a** and the second bond pad isolation layer **114b**. In some embodiments, the first bond pad isolation layer **114a** may, for example, be or comprise silicon dioxide, another suitable oxide, or the like. In further embodiments, the second bond pad isolation layer **114b** may, for example, be or comprise silicon oxynitride, another suitable dielectric material, or the like.

(97) FIG. **39** illustrates a third method **3900** of forming an integrated circuit according to the present disclosure. Although the third method **3900** is illustrated and/or described as a series of acts or events, it will be appreciated that the method is not limited to the illustrated ordering or acts. Thus, in some embodiments, the acts may be carried out in different orders than illustrated, and/or may be carried out concurrently. Further, in some embodiments, the illustrated acts or events may be subdivided into multiple acts or events, which may be carried out at separate times or concurrently with other acts or sub-acts. In some embodiments, some illustrated acts or events may be omitted, and other un-illustrated acts or events may be included.

(98) At act **3902**, a shallow trench isolation (STI) structure is formed on a front-side of a semiconductor substrate. FIG. **32** illustrates a cross-sectional view **3200** corresponding to some embodiments of act **3902**.

(99) At act **3904**, an interconnect structure is formed on the front-side of the semiconductor substrate. The interconnect structure includes an upper conductive wire layer. FIG. **33** illustrates a cross-sectional view **3300** corresponding to some embodiments of act **3904**.

(100) At act **3906**, a dielectric structure is formed over the back-side of the semiconductor substrate. FIG. **33** illustrates a cross-sectional view **3300** corresponding to some embodiments of act **3906**.

(101) At act **3908**, a bond pad isolation structure is formed in the semiconductor substrate and the dielectric structure. The bond pad isolation structure extends from the front-side of the semiconductor substrate to the back-side of the semiconductor substrate. FIGS. **35** and **36** illustrate cross-sectional views **3500** and **3600** corresponding to some embodiments of act **3908**.

(102) At act **3910**, a bond pad is formed in the semiconductor substrate. The bond pad isolation structure continuously extends around the bond pad. FIGS. **37** and **38** illustrate cross-sectional views **3700** and **3800** corresponding to some embodiments of act **3910**.

(103) Accordingly, in some embodiments, the present disclosure relates to a bond pad region laterally offset from a device region. The bond pad region includes a bond pad extending through a semiconductor substrate to an interconnect structure. A bond pad isolation structure is disposed within the semiconductor substrate and continuously surrounds outer sidewalls of the bond pad.

(104) In some embodiments, the present application provides a semiconductor device structure including a semiconductor substrate having a back-side surface and a front-side surface opposite

the back-side surface; a bond pad extending through the semiconductor substrate; and a bond pad isolation structure disposed within the semiconductor substrate, wherein the bond pad isolation structure extends from the front-side surface to the back-side surface of the semiconductor substrate, and wherein the bond pad isolation structure continuously extends around the bond pad.

(105) In some embodiments, the present application provides a semiconductor device structure including a semiconductor substrate overlying a carrier substrate, wherein photodetectors are disposed in the semiconductor substrate; an interconnect structure disposed between the semiconductor substrate and the carrier substrate, wherein an upper conductive wire layer is disposed in the interconnect structure; a bond pad extending through the semiconductor substrate to the interconnect structure, wherein the bond pad contacts the upper conductive wire layer and has a top surface disposed above the semiconductor substrate, wherein the bond pad is laterally offset from the photodetectors; and a bond pad isolation structure disposed within the semiconductor substrate, wherein the bond pad isolation structure continuously wraps around outer sidewalls of the bond pad.

(106) In some embodiments, the present application provides a method for forming a semiconductor device structure, the method includes forming a bond pad isolation structure in a semiconductor substrate, wherein the bond pad isolation structure extends from a front-side surface to a back-side surface of the semiconductor substrate; forming an interconnect structure on the front-side surface of the semiconductor substrate, wherein the interconnect structure includes a conductive wire layer; patterning the front-side surface of the semiconductor substrate to define a bond pad opening and expose an upper surface of the conductive wire layer, wherein the bond pad opening is disposed laterally between inner sidewalls of the bond pad isolation structure; and forming a bond pad in the bond pad opening, wherein the bond pad extends from the semiconductor substrate to the conductive wire layer, and wherein the bond pad isolation structure continuously wraps around the bond pad.

(107) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. An integrated chip comprising: a substrate having an upper surface vertically below a top surface; a dielectric structure contacting the top surface of the substrate; a conductive structure disposed in the substrate, wherein the conductive structure comprises an upper conductive body and conductive protrusions directly underlying the upper conductive body, wherein the upper conductive body overlies the upper surface of the substrate, wherein a bottom surface of the dielectric structure is disposed between a top surface and a bottom surface of the upper conductive body; a first isolation structure disposed in the substrate on opposing sides of the upper conductive body; and a second isolation structure disposed in the substrate and laterally extending between the conductive protrusions, wherein an outer perimeter of the second isolation structure is spaced between inner sidewalls of the first isolation structure.
2. The integrated chip of claim 1, wherein the second isolation structure directly contacts the conductive protrusions.
3. The integrated chip of claim 1, wherein a distance between the upper surface of the substrate and the top surface of the substrate is less than a height of the upper conductive body.

4. The integrated chip of claim 3, wherein a height of the first isolation structure is greater than a height of the conductive protrusions, wherein the height of the conductive protrusions is greater than the distance.
5. The integrated chip of claim 1, further comprising: a plurality of photodetectors disposed within the substrate; a grid structure overlying the dielectric structure and the plurality of photodetectors, wherein the grid structure comprises a first grid layer vertically stacked with a second grid layer, wherein the first grid layer comprises a first material and the second grid layer comprises a second material different from the first material; and a plurality of color filters arranged in the first and second grid layers and over the plurality of photodetectors.
6. The integrated chip of claim 1, wherein when viewed in plan view the first isolation structure is ring-shaped and comprises a curved edge that conforms to a shape of a curved edge of the upper conductive body.
7. The integrated chip of claim 1, wherein the dielectric structure comprises a topmost dielectric layer disposed over one or more lower dielectric layers, wherein the top surface of the upper conductive body is aligned with a top surface of the topmost dielectric layer or is vertically above a bottom surface of the topmost dielectric layer.
8. The integrated chip of claim 1, wherein a top surface of the first isolation structure is disposed between the top and bottom surfaces of the upper conductive body.
9. An integrated chip comprising: a substrate having a front-side surface opposite a back-side surface, wherein the substrate comprises opposing sidewalls extending from the back-side surface to an upper surface of the substrate; a conductive structure spaced between the opposing sidewalls of the substrate, wherein the conductive structure comprises an upper conductive body, a first conductive protrusion, and second conductive protrusion, wherein the upper conductive body has a bottom surface below the back-side surface and overlying the upper surface of the substrate, wherein the first and second conductive protrusions contact and underlie the upper conductive body, wherein a top surface of the upper conductive body is vertically above the front-side surface; a first insulator layer disposed directly between the bottom surface of the upper conductive body and the upper surface of the substrate; a second insulator layer disposed between sidewalls of the first and second conductive protrusions and the substrate; an isolation structure disposed in the substrate, wherein outer sidewalls of the upper conductive body are spaced between inner sidewalls of the isolation structure; a dielectric structure disposed along the back-side surface and over the isolation structure, wherein a top surface of the dielectric structure is aligned with a top surface of the first insulator layer; and a shallow trench isolation (STI) structure between a bottom surface of the second insulator layer and the front-side surface, wherein an outer sidewall of the STI structure is spaced between the inner sidewalls of the isolation structure.
10. The integrated chip of claim 9, wherein a vertical thickness of the dielectric structure is less than a vertical thickness of the upper conductive body.
11. The integrated chip of claim 9, wherein the dielectric structure comprises a first material different from a second material of the isolation structure and different from a third material of the first insulator layer, wherein the first insulator layer contacts opposing sidewalls of the dielectric structure, and wherein outer sidewalls of the first insulator layer are disposed between the inner sidewalls of the isolation structure.
12. The integrated chip of claim 9, wherein the dielectric structure comprises a first dielectric layer, a second dielectric layer, and a third dielectric layer, wherein the first, second, and third dielectric layers comprise different materials, wherein the dielectric structure comprises opposing sidewalls aligned with the opposing sidewalls of the substrate.
13. The integrated chip of claim 9, wherein the second insulator layer directly contacts inner sidewalls of the first insulator layer.
14. The integrated chip of claim 9, wherein a width of the STI structure is less than a distance between the inner sidewalls of the isolation structure.

15. The integrated chip of claim 9, wherein a width of the isolation structure continuously decreases from the back-side surface to the front-side surface.
16. The integrated chip of claim 9, wherein a bottom surface of the STI structure is aligned with a bottom surface of the isolation structure.
17. A method for forming an integrated chip, comprising: forming an isolation structure in a substrate; forming a dielectric structure over a first surface of the substrate; performing a first patterning process on the dielectric structure and the first surface of the substrate to form a plurality of openings extending through the dielectric structure and the substrate; forming filler structures within the openings, wherein upper surfaces of the filler structures are disposed below the first surface; performing a second patterning process on the dielectric structure and the substrate to form opposing sidewalls and an upper surface in the substrate; removing the filler structures; and forming a conductive structure comprising an upper conductive body over the upper surface of the substrate and conductive protrusions within the openings, wherein the isolation structure is disposed on opposing sides of the upper conductive body.
18. The method of claim 17, wherein the isolation structure is formed before forming the dielectric structure.
19. The method of claim 17, wherein after the second patterning process, the upper surfaces of the filler structures are above the upper surface of the substrate.
20. The method of claim 17, wherein forming the isolation structure comprises: etching the substrate and the dielectric structure to form isolation openings extending through the dielectric structure and the substrate; depositing an isolation layer over the dielectric structure and filling the isolation openings; and performing a planarization process on the isolation layer.
-