

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12416863
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Dai; Yuqiong et al.

Dry develop process of photoresist

Abstract

Embodiments disclosed herein include a method of developing a metal oxo photoresist with a non-wet process. In an embodiment, the method comprises providing a substrate with the metal oxo photoresist into a chamber. In an embodiment, the metal oxo photoresist comprises exposed regions and unexposed regions, and the unexposed regions comprise a higher carbon concentration than the exposed regions. In an embodiment, the method further comprises flowing a gas into the chamber, wherein the gas reacts with the unexposed regions to produce a volatile byproduct.

Inventors: Dai; Yuqiong (Santa Clara, CA), Sachan; Madhur (Belmont, CA), Freed; Regina (Los Altos, CA), Hwang; Hoyung David (Cupertino, CA)

Applicant: Applied Materials, Inc. (Santa Clara, CA)

Family ID: 1000008819549

Assignee: Applied Materials, Inc. (Santa Clara, CA)

Appl. No.: 17/349534

Filed: June 16, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220004105 A1	Jan. 06, 2022

Related U.S. Application Data

us-provisional-application US 63047160 20200701

Publication Classification

Int. Cl.: G03F7/40 (20060101); **C23C16/06** (20060101); **G03F7/004** (20060101); **G03F7/16** (20060101); **G03F7/20** (20060101)

U.S. Cl.:

CPC G03F7/40 (20130101); **C23C16/06** (20130101); **G03F7/0047** (20130101); **G03F7/162** (20130101); **G03F7/20** (20130101);

Field of Classification Search

CPC: G03F (7/40); G03F (7/0047); G03F (7/162); G03F (7/20); G03F (7/0042); G03F (7/0043); G03F (7/36); C23C (16/06)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3837944	12/1973	Cole, Jr.	N/A	N/A
4283482	12/1980	Hattori et al.	N/A	N/A
4292384	12/1980	Straughan et al.	N/A	N/A
4320191	12/1981	Yoshikawa et al.	N/A	N/A
4332879	12/1981	Pastor et al.	N/A	N/A
4464455	12/1983	Yoneda et al.	N/A	N/A
4560641	12/1984	Kokaku et al.	N/A	N/A
4842989	12/1988	Taniguchi et al.	N/A	N/A
5310624	12/1993	Ehrlich	N/A	N/A
5366852	12/1993	Pavelchek et al.	N/A	N/A
5439780	12/1994	Joshi et al.	N/A	N/A
5457005	12/1994	Babich	430/296	G03F 7/0755
5763016	12/1997	Levenson et al.	N/A	N/A
5885751	12/1998	Weidman et al.	N/A	N/A
6204168	12/2000	Naik et al.	N/A	N/A
6589715	12/2002	Joubert et al.	N/A	N/A
6825562	12/2003	Naik et al.	N/A	N/A
6855485	12/2004	Irie	N/A	N/A
6989227	12/2005	Weldman et al.	N/A	N/A
7064076	12/2005	Kulkarni	N/A	N/A
7713678	12/2009	Hosoda	N/A	N/A
7771895	12/2009	Wu et al.	N/A	N/A
8465903	12/2012	Weidman et al.	N/A	N/A
8536068	12/2012	Weidman et al.	N/A	N/A
8709706	12/2013	Wu et al.	N/A	N/A
8940386	12/2014	Ohtani et al.	N/A	N/A
9229326	12/2015	Lu	N/A	H01L 21/0332
9310684	12/2015	Meyers et al.	N/A	N/A
9354508	12/2015	Beasley et al.	N/A	N/A
9411237	12/2015	Xie et al.	N/A	N/A

9417515	12/2015	Barman et al.	N/A	N/A
9470980	12/2015	Inoue et al.	N/A	N/A
9632411	12/2016	Michaelson et al.	N/A	N/A
9778561	12/2016	Marks et al.	N/A	N/A
9829805	12/2016	Michaelson et al.	N/A	N/A
9996004	12/2017	Smith et al.	N/A	N/A
10228618	12/2018	Meyers et al.	N/A	N/A
10642153	12/2019	Meyers et al.	N/A	N/A
10658180	12/2019	Mignot et al.	N/A	N/A
10787466	12/2019	Edson et al.	N/A	N/A
10831096	12/2019	Marks et al.	N/A	N/A
11599022	12/2022	Stowers et al.	N/A	N/A
11621172	12/2022	Kalutarage et al.	N/A	N/A
2001/0008227	12/2000	Sadamoto	216/75	H01L 21/32136
2001/0009154	12/2000	Nguyen et al.	N/A	N/A
2004/0091618	12/2003	Park et al.	N/A	N/A
2004/0214113	12/2003	Goldstein et al.	N/A	N/A
2008/0014533	12/2007	Keller et al.	N/A	N/A
2011/0294072	12/2010	Park	430/323	H01L 21/0273
2012/0088193	12/2011	Weidman et al.	N/A	N/A
2012/0322015	12/2011	Kim	N/A	N/A
2014/0263172	12/2013	Xie et al.	N/A	N/A
2014/0356770	12/2013	Hayashi	N/A	N/A
2015/0056542	12/2014	Meyers	430/296	G03F 7/2002
2015/0200091	12/2014	Chada	438/694	H01L 21/31133
2015/0270140	12/2014	Gupta et al.	N/A	N/A
2016/0011502	12/2015	Hofmann et al.	N/A	N/A
2016/0116839	12/2015	Meyers et al.	N/A	N/A
2016/0329222	12/2015	Xie et al.	N/A	N/A
2016/0379833	12/2015	Hong et al.	N/A	N/A
2017/0146909	12/2016	Smith	N/A	G03F 7/2004
2017/0186614	12/2016	Ko et al.	N/A	N/A
2017/0261850	12/2016	Stowers	N/A	H01L 21/0338
2017/0271152	12/2016	Char et al.	N/A	N/A
2018/0138054	12/2017	Romero et al.	N/A	N/A
2018/0173096	12/2017	Zi et al.	N/A	N/A
2018/0307137	12/2017	Meyers et al.	N/A	N/A
2019/0131130	12/2018	Smith et al.	N/A	N/A
2019/0153001	12/2018	Cardineau et al.	N/A	N/A
2019/0198325	12/2018	Briggs et al.	N/A	N/A
2019/0308998	12/2018	Cardineau et al.	N/A	N/A
2019/0315781	12/2018	Edson et al.	N/A	N/A

2019/0337969	12/2018	Odedra et al.	N/A	N/A
2019/0384171	12/2018	Zi et al.	N/A	N/A
2020/0051807	12/2019	Singhal et al.	N/A	N/A
2020/0064733	12/2019	Meyers et al.	N/A	N/A
2020/0073238	12/2019	Zi et al.	N/A	N/A
2020/0176246	12/2019	Huotari et al.	N/A	N/A
2020/0223877	12/2019	Odedra et al.	N/A	N/A
2020/0239498	12/2019	Clark et al.	N/A	N/A
2020/0241413	12/2019	Clark et al.	N/A	N/A
2020/0326627	12/2019	Jiang et al.	N/A	N/A
2021/0305028	12/2020	Guo et al.	N/A	N/A
2022/0020584	12/2021	Voloskiy et al.	N/A	N/A
2022/0004105	12/2021	Dai et al.	N/A	N/A
2022/0244645	12/2021	Tan et al.	N/A	N/A
2022/0306657	12/2021	Fabulyak et al.	N/A	N/A
2022/0308447	12/2021	Stowers et al.	N/A	N/A
2022/0344136	12/2021	Peter	N/A	G03F 7/167
2023/0019943	12/2022	Nakabayashi et al.	N/A	N/A
2023/0078946	12/2022	Grzeskowiak et al.	N/A	N/A
2023/0091094	12/2022	Huotari et al.	N/A	N/A
2023/0100995	12/2022	Cardineau et al.	N/A	N/A
2023/0143629	12/2022	Clark	N/A	N/A
2023/0152705	12/2022	Grzeskowiak et al.	N/A	N/A
2023/0197505	12/2022	Lutker-Lee et al.	N/A	N/A
2023/0215736	12/2022	Kalutarage et al.	N/A	N/A
2023/0290646	12/2022	Kalutarage et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
108351594	12/2017	CN	N/A
0090615	12/1982	EP	N/A
0100079	12/1983	EP	N/A
1033744	12/1999	EP	N/A
2926199	12/2019	EP	N/A
05100425	12/1992	JP	G03F 7/0755
08320574	12/1995	JP	N/A
2014209622	12/2013	JP	N/A
2017116923	12/2016	JP	N/A
2019500490	12/2018	JP	N/A
2020510994	12/2019	JP	H01L 21/02175
2022538040	12/2021	JP	N/A
2022538554	12/2021	JP	N/A
1020220025020	12/2021	KR	N/A
1020220025885	12/2021	KR	N/A

1020237003446	12/2022	KR	N/A
201443271	12/2013	TW	N/A
201601444	12/2015	TW	N/A
201635334	12/2015	TW	N/A
201841258	12/2017	TW	N/A
201842573	12/2017	TW	N/A
2020/06168	12/2019	TW	N/A
202006168	12/2019	TW	N/A
202016279	12/2019	TW	N/A
202117468	12/2020	TW	N/A
202205013	12/2021	TW	N/A
202219632	12/2021	TW	N/A
WO 2004-095551	12/2003	WO	N/A
WO 2018-004646	12/2017	WO	N/A
2019217749	12/2018	WO	N/A
2020081483	12/2019	WO	N/A
WO 2020-132281	12/2019	WO	N/A
WO-2020132281	12/2019	WO	G03F 7/162
2020264571	12/2019	WO	N/A
WO 2020-264158	12/2019	WO	N/A
WO 2020-264557	12/2019	WO	N/A
WO-2020264158	12/2019	WO	G03F 7/0042
WO 2021-072042	12/2020	WO	N/A
WO 2021-146138	12/2020	WO	N/A
2021158433	12/2020	WO	N/A
WO 2021-202146	12/2020	WO	N/A
WO-2022016127	12/2021	WO	G03F 7/0043
2022103764	12/2021	WO	N/A
2022125388	12/2021	WO	N/A
2022265874	12/2021	WO	N/A
2023/009364	12/2022	WO	N/A
2023089946	12/2022	WO	N/A

OTHER PUBLICATIONS

Krysak, Marie, et al. "Development of an inorganic nanoparticle photoresist for EUV, e-beam, and 193nm lithography." In *Advances in Resist Materials and Processing Technology XXVIII* (vol. 7972, pp. 408-413). SPIE, 2011. (Year: 2011). cited by examiner

Cardineau, Brian, et al. "EUV resists based on tin-oxo clusters." In *Advances in Patterning Materials and Processes XXXI* (vol. 9051, pp. 335-346). SPIE, 2014. (Year: 2014). cited by examiner

Buitrago, Elizabeth, et al. "SnOx high-efficiency EUV interference lithography gratings towards the ultimate resolution in photolithography." *Microelectronic Engineering* 155 (2016): 44-49. (Year: 2016). cited by examiner

Honewell, "List of Reactive Gases." (2019) (Year: 2019). cited by examiner

Niibe, Masahito, and Keigo Koida. "Competitive reactions of carbon deposition and oxidation on the surface of Mo/Si multilayer mirrors by EUV irradiation." *Damage to VUV, EUV, and X-Ray Optics II*. vol. 7361. SPIE. (Year: 2009). cited by examiner

Preliminary Report on Patentability for Patent Application No. PCT/US2021/038758 dated Jan. 12,

2023, 6 pgs. cited by applicant

International Search Report and Written Opinion from International Patent Application No.

PCT/US2021/038758 dated Oct. 15, 2021, 10 pgs. cited by applicant

Official Letter from Taiwan Patent Application No. 110123956 dated Jun. 2, 2023, 12 pgs. cited by applicant

Floy Chang, et al., "Gas-phase Silicon micromachining with xenon difluoride", Proceedings of SPIE, Downloaded from: <https://www.spiedigitallibrary.org/conference-proceedings-of-spie>. Jul. 13, 2023, pp. 117-128. cited by applicant

Shigeyasu Mori, et al., "Prediction of Resolution using wet-develop type single layer and dry-development process for EUV lithography", Microelectronic Engineering 53 (2000), pp. 689-692. cited by applicant

Gediminas Seniutinas, "Development of high-resolution 3D nanotechnology tools: sensors focus", Faculty of Science, Engineering and Technology, Swinburne University of Technology, 2016, pp. 1-82, 91-123, 129-187, 213-261. cited by applicant

Hiroshi Ito, et al. "Chemical Amplification in the Design of Dry Developing Resist Materials", Polymer Engineering and Science, Dec. 1983, vol. 23, No. 18, pp. 1012-1018. cited by applicant

Theodore Manouras, et al. "High Sensitivity Resists for EUV Lithography: A Review of Material Design Strategies and Performance Results". nanomaterials Aug. 14, 2020, pp. 1-24. cited by applicant

Jason K. Stowers, "Direct Patterning of Solution Deposited Metal Oxides", Aug. 14, 2008, pp. 1-149. cited by applicant

T.W. Weidman, et al. "Applications of Plasma Polymerized Methylsilane as a Resist and Silicon Dioxide Precursor for 193 and 248 nm Lithography", SPIE vol. 2438. Jun. 9, 1995, pp. 496-503. cited by applicant

Matthew L. Wagner, et al. "The Use of HBr in Polysilicon Etching", Gases & Instrumentation International, vol. 7, Issue 4, Jul./Aug. 2013, pp. 1-7. cited by applicant

Notice of Reasons for Rejection from Japanese Patent Application No. 2022-580826 dated Feb. 26, 2024, 8 pgs. cited by applicant

Official Action from Taiwan Patent Application No. 112128099 dated Mar. 22, 2024, 5 pgs. cited by applicant

Official Action from Taiwan Patent Application No. 110123956 dated Apr. 16, 2024, 12 pgs. cited by applicant

International Search Report and Written Opinion from PCT/US2023/032497 dated Jan. 3, 2024, 9 pgs. cited by applicant

Official Letter from Taiwan Patent Application No. 112128099 dated Dec. 22, 2023, 6 pgs. cited by applicant

Notice of Reasons for Rejection from Japanese Patent Application No. 2022-580825 dated Jan. 23, 2024, 8 pgs. cited by applicant

Official Letter from Taiwan Patent Application No. 112128099 dated Sep. 22, 2023, 6 pgs. cited by applicant

Official Letter from Taiwan Patent Application No. 110124241 dated Mar. 28, 2023, 10 pgs. cited by applicant

International Search Report and Written Opinion from PCT/US2021/038424 dated Oct. 14, 2021, 9 pgs. cited by applicant

Non-Final Office Action from U.S. Appl. No. 18/198,743 dated Dec. 5, 2023, 28 pgs. cited by applicant

Non-Final Office Action from U.S. Appl. No. 17/348,589 dated Jul. 28, 2022, 11 pgs. cited by applicant

International Preliminary Report on Patentability from PCT/US2021/038424 dated Jan. 12, 2023, 6 pgs. cited by applicant

Non-Final Office Action from U.S. Appl. No. 18/116,556 dated Aug. 1, 2023, 9 pgs. cited by applicant
Non-Final Office Action from U.S. Appl. No. 18/116,556 dated Dec. 5, 2023, 25 pgs. cited by applicant
Final Office Action from U.S. Appl. No. 18/198,743 dated Mar. 6, 2024, 20 pgs. cited by applicant
International Search Report and Written Opinion from PCT/US2024/012192 dated May 13, 2024, 10 pgs. cited by applicant
Notice to File a Response from Korean Patent Application No. 10-2023-7003446 dated Jun. 19, 2024, 6 pgs. cited by applicant
International Search Report and Written Opinion from PCT/US2024/032380 dated Sep. 13, 2024, 7 pgs. cited by applicant
Notice to File a Response from Korean Patent Application No. 10-2023-7025985 dated Jul. 8, 2024, 12 pgs. cited by applicant
Preliminary Rejection from Korean Patent Application No. 10-2023-7003603 dated Jun. 26, 2024, 12 pgs. cited by applicant
Notice of Reasons for Rejection from Japanese Patent Application No. 2023-118745 dated Jul. 6, 2024, 8 pgs. cited by applicant
International Preliminary Report on Patentability from PCT/US2023/032497 dated May 22, 2025, 6 pgs. cited by applicant
Official Letter from Taiwan Patent Application No. 113149091 dated Jun. 23, 2025, 12 pgs. cited by applicant
Official Letter from Taiwan Patent Application No. 112134987 dated Jun. 12, 2025, 17 pgs. cited by applicant

Primary Examiner: Huff; Mark F.

Assistant Examiner: Smoot; Moriah S.

Attorney, Agent or Firm: Schwabe, Williamson & Wyatt, P.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application claims the benefit of U.S. Provisional Application No. 63/047,160, filed on Jul. 1, 2020, the entire contents of which are hereby incorporated by reference herein.

BACKGROUND

1) Field

(1) Embodiments of the present disclosure pertain to the field of semiconductor processing and, in particular, to methods of patterning a metal oxo photoresist using a non-wet process.

2) Description of Related Art

(2) Lithography has been used in the semiconductor industry for decades for creating 2D and 3D patterns in microelectronic devices. The lithography process involves spin-on deposition of a film (photoresist), irradiation of the film with a selected pattern by an energy source (exposure), and removal (etch) of exposed (positive tone) or non-exposed (negative tone) region of the film by dissolving in a solvent. A bake will be carried out to drive off remaining solvent.

(3) The photoresist should be a radiation sensitive material and upon irradiation a chemical transformation occurs in the exposed part of the film which enables a change in solubility between exposed and non-exposed regions. Using this solubility change, either exposed or non-exposed

regions of the photoresist is removed (developed). As used herein, “develop” refers to a process of forming a pattern into the photoresist. Now the photoresist is developed and the pattern can be transferred to the underlying thin film or substrate by etching. After the pattern is transferred, the residual photoresist is removed and repeating this process many times can give 2D and 3D structures to be used in microelectronic devices.

(4) Several properties are important in lithography processes. Such important properties include sensitivity, resolution, lower line-edge roughness (LER), etch resistance, and ability to form thinner layers. When the sensitivity is higher, the energy required to change the solubility of the as-deposited film is lower. This enables higher efficiency in the lithographic process. Resolution and LER determine how narrow features can be achieved by the lithographic process. Higher etch resistant materials are required for pattern transferring to form deep structures. Higher etch resistant materials also enable thinner films. Thinner films increase the efficiency of the lithographic process.

SUMMARY

(5) Embodiments disclosed herein include a method of developing a metal oxo photoresist with a non-wet process. In an embodiment, the method comprises providing a substrate with the metal oxo photoresist into a chamber. In an embodiment, the metal oxo photoresist comprises exposed regions and unexposed regions, and the unexposed regions comprise a higher carbon concentration than the exposed regions. In an embodiment, the method further comprises flowing a gas into the chamber, wherein the gas reacts with the unexposed regions to produce a volatile byproduct.

(6) Embodiments may also include a method of developing a metal oxo photoresist that comprises providing a substrate with the metal oxo photoresist on a surface of the substrate, and exposing the metal oxo photoresist to form exposed regions and unexposed regions. In an embodiment, the unexposed regions comprise a higher carbon concentration than the exposed regions. In an embodiment, the method may further comprise placing the substrate in a plasma chamber, flowing a gas into the plasma chamber, and striking a plasma in the plasma chamber. In an embodiment, the plasma reacts with the unexposed regions to produce a volatile byproduct. In an embodiment, the method may further comprise purging the plasma chamber.

(7) Embodiments may also include a method of developing a metal oxo photoresist that comprises providing a substrate with the metal oxo photoresist into a plasma chamber, where the metal oxo photoresist comprises SnOC. In an embodiment, the metal oxo photoresist comprises exposed regions and unexposed regions, and the unexposed regions comprise a higher carbon concentration than the exposed regions. In an embodiment, the method further comprises flowing a gas into the plasma chamber, where the gas comprises Cl.sub.2 and Ar, and striking a plasma in the plasma chamber. In an embodiment, the plasma reacts with the unexposed regions to produce a volatile byproduct. The method may further comprise purging the plasma chamber.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a flowchart describing a process for developing a metal oxo photoresist using a plasma process, in accordance with an embodiment of the present disclosure.

(2) FIGS. 2A-2D are cross-sectional illustrations of a substrate and a photoresist depicting operations in the flowchart of FIG. 1, in accordance with an embodiment of the present disclosure.

(3) FIG. 3 is a cross-sectional illustration of a processing tool that may be used to implement portions of the process in FIG. 1, in accordance with an embodiment of the present disclosure.

(4) FIG. 4 illustrates a block diagram of an exemplary computer system, in accordance with an embodiment of the present disclosure.

DETAILED DESCRIPTION

(5) Methods of patterning a metal oxo photoresist using non-wet processes are described herein. In the following description, numerous specific details are set forth, such as reactive plasma processes and material regimes for developing photoresist, in order to provide a thorough understanding of embodiments of the present disclosure. It will be apparent to one skilled in the art that embodiments of the present disclosure may be practiced without these specific details. In other instances, well-known aspects, such as integrated circuit fabrication, are not described in detail in order to not unnecessarily obscure embodiments of the present disclosure. Furthermore, it is to be understood that the various embodiments shown in the Figures are illustrative representations and are not necessarily drawn to scale.

(6) To provide context, photoresist systems used in extreme ultraviolet (EUV) lithography suffer from low efficiency. That is, existing photoresist material systems for EUV lithography require high dosages in order to provide the needed solubility switch that allows for developing the photoresist material. Organic-inorganic hybrid materials (e.g., metal oxo materials systems) have been proposed as a material system for EUV lithography due to the increased sensitivity to EUV radiation. Such material systems typically comprise a metal (e.g., Sn, Hf, Zr, etc.), oxygen, and carbon. In some instances, the metal oxo material system may further comprise nitrogen and hydrogen. Metal oxo based organic-inorganic hybrid materials have also been shown to provide lower LER and higher resolution, which are required characteristics for forming narrow features.

(7) In a metal oxo photoresist system, exposure to EUV radiation results in the removal of carbon and the cross-linking of the metal oxide network. The difference in the carbon percentage and bonding strength between the exposed regions and the unexposed regions is used as the solubility switch during developing. Particularly, the unexposed regions with the higher carbon content and weaker bond strength are preferentially etched by the developer solution.

(8) Metal oxo photoresist systems are currently developed using a wet chemistry. That is, after exposure, the unexposed regions of the photoresist are developed by organic solvents/base solution that is used with a spin-dry process. A post-bake anneal may also be included. However, wet methods can be troublesome when dealing with high aspect ratio features due to the risk of pattern collapse (especially in line or pillar structures). Additionally, wet processes might not remove all of the material that is supposed to be removed and film materials/byproducts/solvents and the like may be trapped in small features since a mechanical force is used to remove the solvent and dissolved byproducts. Furthermore, with smaller and more complicated features, it is harder for the solvent (which is usually a larger molecule) to penetrate all areas of the unexposed resist. This leads to a partial develop of the photoresist and causes defects. The spin-dry process may also result in line wiggling and even falling off. This limits the photoresist thickness and aspect ratio.

(9) Accordingly, embodiments of the present disclosure provide a plasma etching process to develop metal oxo photoresists. Particularly, plasma etching processes provide the advantages of: 1) eliminating the generation of wet byproducts; 2) lower waste streams due to dry chemistry being processed through an abatement system; 3) providing fewer defects and impurities; 4) improvement of LER, LWR, and any low frequency roughness originating from surface tension, capillary forces, and spin-dry processes; 5) providing an all-in-one-process for developing a photoresist and transferring the pattern into the underlayer; and 6) providing a high etch selectivity of the unexposed regions to the exposed regions of the metal oxo photoresist.

(10) Embodiments disclosed herein provide a plasma etching process that is executed after portions of a metal oxo photoresist are exposed with a suitable electromagnetic radiation source (e.g., an EUV source). In an embodiment, a substrate comprising an exposed metal oxo photoresist is placed in a plasma chamber. A gas comprising a reactive gas and an inert gas is flown into the plasma chamber, and a plasma is struck. The reactive gas is a gas with constituents that react with the metal of the metal oxo photoresist to form a volatile species. For example, the reactive gas comprises one or more of Cl_{sub.2}, H_{sub.2}, Br_{sub.2}, HBr, HCl, BCl_{sub.3}, CH_{sub.x}Cl_{sub.y}, CH_{sub.4}, BBr_{sub.3}, and CH_{sub.x}Br_{sub.y}. In a particular embodiment, the reactive gas comprises HBr and

the inert gas comprises Ar. In some embodiments, the gas is flown into a chamber without striking a plasma (i.e., a thermal process). In other embodiments, a plasma may be struck. In an embodiment, an etch selectivity of the unexposed metal oxo photoresist to the exposed metal oxo photoresist may be 10:1 or greater. In a particular embodiment, the etch selectivity is approximately 12:1. In an embodiment, the pattern of the developed metal oxo photoresist may be transferred into the underlayer without removing the substrate from the plasma chamber.

(11) Referring now to FIG. 1, a flowchart illustrating a process **120** for developing a metal oxo photoresist on a substrate surface is provided, in accordance with an embodiment of the present disclosure. FIGS. 2A-2D are cross-sectional illustrations of a substrate **261** and a metal oxo photoresist **262** after various operations in process **120**.

(12) In an embodiment, process **120** may begin with operation **121** which comprises providing a substrate with a metal oxo photoresist. FIG. 2A is a cross-sectional illustration of a substrate **261** with a metal oxo photoresist **262** disposed over a surface of the substrate **261**. In an embodiment, the substrate **261** may comprise any substrate material or materials typical of semiconductor manufacturing environments. For example, the substrate **261** may comprise a semiconducting material. Substrate **261** may comprise semiconductor devices or portions of semiconductor devices. Examples of such semiconductor devices include, but are not limited to, memory devices or complimentary metal-oxide-semiconductor (CMOS) transistors fabricated in a silicon substrate and encased in a dielectric layer. The substrate **261** may also comprise a plurality of metal interconnects formed above the devices or transistors, and in surrounding dielectric layers, and may be used to electrically couple the devices or transistors to form integrated circuits. In an embodiment, the substrate **261** may be a wafer.

(13) In an embodiment, the metal oxo photoresist **262** (also referred to simply as “photoresist **262**”), may be any metal oxo material system. Such material systems typically comprise a metal (e.g., Sn, Hf, Zr, etc.), oxygen, and carbon. In a particular embodiment, the photoresist **262**, comprises SnOC. In addition to SnOC, embodiments may comprise a metal oxo material system that further comprises nitrogen and hydrogen.

(14) The photoresist **262** may be disposed over the surface of the substrate **261** using any suitable deposition process. In an embodiment, the photoresist is disposed on the surface of the substrate **261** with a wet chemistry using a spin-on process. In an alternative embodiment, the photoresist is disposed on the surface of the substrate **261** using a vapor phase process (i.e., a dry process). In a vapor phase process, a metal precursor and an oxidant may be vaporized to a vacuum chamber, with the metal precursor and the oxidant reacting to deposit a metal oxo photoresist **262** on the surface of the substrate **261**. Such dry processes may be characterized as a chemical vapor deposition (CVD) process, an atomic layer deposition (ALD) process, a plasma enhanced CVD (PE-CVD) process, or a plasma enhanced ALD (PE-ALD) process.

(15) In an embodiment, process **120** may continue with operation **122** which comprises exposing portions of the metal oxo photoresist to create exposed regions and unexposed regions. FIG. 2B is a cross-sectional illustration depicting the exposure process. As shown, electromagnetic radiation **264** passes through a mask **263** to expose the exposed regions **262.sub.E**. The unexposed regions **262.sub.U** are blocked from the electromagnetic radiation by the mask **263**. In an embodiment, the electromagnetic radiation is EUV radiation. When EUV radiation is used, the EUV radiation **264** may be reflected off the mask instead of passing through the mask. While EUV radiation is specifically disclosed herein, it is to be appreciated that any suitable wavelength of electromagnetic radiation that can initiate a solubility switch in the metal oxo photoresist **262** may be used. For example, DUV radiation may be used in some embodiments.

(16) In an embodiment, the solubility switch is provided by the loss of carbon and cross-linking of the metal oxo network in the exposed regions. Particularly, the exposure to electromagnetic radiation results in the removal of carbon from the exposed regions **262.sub.E**. The higher the carbon content and more of the weaker bonds in the unexposed regions **262.sub.U** renders the

unexposed regions more susceptible to patterning in the subsequent non-wet development process. (17) In an embodiment, process **120** may continue with operation **123** which comprises placing the substrate into a plasma chamber. In an embodiment, the plasma chamber may be any suitable chamber for striking a plasma in sub-atmospheric pressure conditions. The plasma chamber may also include heating/cooling features to provide thermal control of the plasma process. For example, a chuck on which the substrate **261** is placed may be an actively heated and/or cooled chuck. Additionally, walls of the plasma chamber may be actively heated and/or cooled in some embodiments. A more detailed description of a suitable plasma chamber is provided below with respect to FIG. 7.

(18) In an embodiment, process **120** may continue with operations **124** and **125** which comprise flowing a gas into the plasma chamber and striking a plasma in the plasma chamber. In an embodiment, the gas comprises a reactive gas and an inert gas. The reactive gas may comprise one or more of Cl.sub.2, Br.sub.2, HBr, HCl, H.sub.2, BCl.sub.3, CH.sub.xCl.sub.y, CH.sub.4, BBr.sub.3, and CH.sub.xBr.sub.y. In an embodiment, the inert gas may comprise Ar, N.sub.2, or He. In a particular embodiment, the reactive gas comprises HBr and the inert gas comprises Ar. In an embodiment, the plasma formed by the reactive gas reacts with the unexposed regions of the metal oxo photoresist **262.sub.U** to form a volatile byproduct. For example, metal M (e.g., Sn) and Cl will react to form volatile MCl.sub.4. An example of a developed photoresist after conversion of the unexposed regions **262.sub.U** into a volatile byproduct is shown in FIG. 2C. It is to be appreciated that striking a plasma is optional. That is, in some embodiments, a non-wet process may comprise flowing the reactive gas into the chamber without striking a plasma. Such a process may be considered a thermal process as opposed to a plasma process. In such instances, the reactive gas may directly react with the unexposed regions of the metal oxo photoresist **262.sub.U** without the need for ionizing the reactive gas.

(19) In an embodiment, a ratio of a flowrate of the inert gas to a flowrate of the reactive gas is between 0:1 and 50:1. For example, a flowrate of the inert gas may be 300 sccm and a flowrate of the reactive gas may be 50 sccm. A dilute chemistry slows the etch rate and improves etching uniformity. Uniformity is improved because the inert gas helps to uniformly distribute the reactive gas throughout the plasma chamber. Additionally, it has been generally shown that increases in the flowrate of the reactive gas provides an increase in the etching of the unexposed regions **262.sub.U** relative to the exposed regions **262.sub.E**. In an embodiment, the pressure may be between approximately 1 mtorr and approximately 100 mtorr. In a particular embodiment, the pressure may be between approximately 5 mtorr and approximately 20 mtorr. In yet another embodiment, the pressure may be between approximately 1 mtorr and approximately 10 torr.

(20) In an embodiment, the substrate **261** may have a controlled temperature during operations **124** and **125**. For example, the temperature may vary between approximately 0° C. and approximately 500° C. In a particular embodiment, the temperature may vary between approximately 50° C. and approximately 150° C. Generally, lower temperatures (e.g., less than 500° C.) are beneficial since the metal oxo photoresist does not thermally decompose at the lower temperatures. In yet another embodiment, the temperature may be less than approximately 200° C. For example, the temperature may be between approximately 40° C. and approximately 100° C.

(21) In an embodiment, RF power of the plasma etching process may be controlled. Generally, a lower RF power may result in improved etch selectivity. In an embodiment, the source power may be between approximately 200 W and approximately 1200 W. In a particular embodiment, the source power may be approximately 400 W. In an embodiment, the bias power may be between approximately 0 W and approximately 200 W. In a particular embodiment, the bias power may be approximately 50 W. It has been shown that increases of the bias power up to approximately 100 W provides enhanced etching selectivity of the unexposed regions **262.sub.U** relative to the exposed regions **262.sub.E**.

(22) In an embodiment, operation **125** may be implemented with a pulsed bias. The duty cycle of

the pulsing may be between 0% and 100%. In a particular embodiment, the duty cycle is approximately 50%. Such a duty cycle allows time for byproduct removal and provides less ion bombardment. Accordingly, etch selectivity of the unexposed regions **262.sub.U** relative to the exposed regions **262.sub.E** is improved.

(23) In an embodiment, operation **125** may be implemented for any desired duration of time. Longer periods of time allow for more of the unexposed regions **262.sub.U** to be removed. In an embodiment, operation **125** may have a duration between approximately 5 seconds and approximately 120 seconds. In a particular embodiment, operations **125** may have a duration of approximately 15 seconds.

(24) By varying various parameters of the plasma development process, such as those described above, a high etch selectivity of the unexposed regions of the metal oxo photoresist **262.sub.U** to the exposed regions of the metal oxo photoresist **262.sub.E** is provided. For example, the etch selectivity may be approximately 10:1 or greater. In a particular embodiment, the etch selectivity may be approximately 12:1. A high etch selectivity provides several benefits. One such benefit is that the thickness of the photoresist may be reduced. This allows for lower doses of electromagnetic radiation to be used in order to fully develop the photoresist.

(25) In an embodiment process **120** may continue with operation **126** which comprises purging the plasma chamber. Purging the plasma chamber removes the byproducts from the reaction in operation **125** from the plasma chamber. In an embodiment, a single purge may be implemented after the completion of the etching in operation **125**. In alternative embodiments, operations **124/125** and **126** may define a cycle comprising a pulse of the etching followed by a purge. In such embodiments, a plurality of cycles may be repeated in order to clear the unexposed regions of the photoresist **262.sub.U**.

(26) Embodiments disclosed herein provide the additional benefit of being implemented in a plasma chamber. This is especially beneficial when the subsequent patterning of the substrate **261** is executed using a plasma etch. Particularly, the substrate **261** does not need to be removed from the plasma chamber following the photoresist developing process. That is, an all-in-one (i.e., all-in-one chamber) solution for pattern development and pattern transfer into the underlayer is provided.

(27) In an embodiment, process **120** may continue with optional operation **127** which comprises etching the substrate **261**. FIG. 2D is a cross-sectional illustration of the substrate **261** after the pattern of the exposed regions of the metal oxo photoresist **262.sub.E** is transferred into the substrate **261**. As shown, the pattern transfer may result in the formation of trenches **265** into the substrate **261**. In an embodiment, the etching of the substrate **261** may be implemented using a plasma etching process. The plasma etching process may be executed in the same chamber that is used to develop the metal oxo photoresist.

(28) FIG. 3 is a schematic of a plasma chamber configured to perform a plasma based development of a metal oxo photoresist, in accordance with an embodiment of the present disclosure. Plasma chamber **300** includes a grounded chamber **305**. A substrate **310** is loaded through an opening **315** and clamped to a temperature controlled chuck **320**.

(29) Process gases, are supplied from gas sources **344** through respective mass flow controllers **349** to the interior of the chamber **305**. In certain embodiments, a gas distribution plate **335** provides for distribution of process gases **344**, such as Cl.sub.2, Br.sub.2, H.sub.2, HCl, HBr, and/or an inert gas. Chamber **305** is evacuated via an exhaust pump **355**.

(30) When RF power is applied during processing of a substrate **310**, a plasma is formed in chamber processing region over substrate **310**. Bias power RF generator **325** is coupled to the temperature controlled chuck **320**. Bias power RF generator **325** provides bias power, if desired, to energize the plasma. Bias power RF generator **325** may have a low frequency between about 2 MHz to 60 MHz for example, and in a particular embodiment, is in the 13.56 MHz band. In certain embodiments, the plasma chamber **300** includes a third bias power RF generator **326** at a frequency at about the 2 MHz band which is connected to the same RF match **327** as bias power RF generator

325. Source power RF generator **330** is coupled through a match (not depicted) to a plasma generating element (e.g., gas distribution plate **335**) to provide a source power to energize the plasma. Source RF generator **330** may have a frequency between 100 and 180 MHz, for example, and in a particular embodiment, is in the 162 MHz band. Because substrate diameters have progressed over time, from 150 mm, 200 mm, 300 mm, etc., it is common in the art to normalize the source and bias power of a plasma etch system to the substrate area.

(31) The plasma chamber **300** is controlled by controller **370**. The controller **370** may comprise a CPU **372**, a memory **373**, and an I/O interface **374**. The CPU **372** may execute processing operations within the plasma chamber **300** in accordance with instructions stored in the memory **373**. For example, one or more processes such as portions of process **120** described above may be executed in the plasma chamber by the controller **370**.

(32) FIG. **4** illustrates a diagrammatic representation of a machine in the exemplary form of a computer system **400** within which a set of instructions, for causing the machine to perform any one or more of the methodologies described herein, may be executed. In alternative embodiments, the machine may be connected (e.g., networked) to other machines in a Local Area Network (LAN), an intranet, an extranet, or the Internet. The machine may operate in the capacity of a server or a client machine in a client-server network environment, or as a peer machine in a peer-to-peer (or distributed) network environment. The machine may be a personal computer (PC), a tablet PC, a set-top box (STB), a Personal Digital Assistant (PDA), a cellular telephone, a web appliance, a server, a network router, switch or bridge, or any machine capable of executing a set of instructions (sequential or otherwise) that specify actions to be taken by that machine. Further, while only a single machine is illustrated, the term “machine” shall also be taken to include any collection of machines (e.g., computers) that individually or jointly execute a set (or multiple sets) of instructions to perform any one or more of the methodologies described herein.

(33) The exemplary computer system **400** includes a processor **402**, a main memory **404** (e.g., read-only memory (ROM), flash memory, dynamic random access memory (DRAM) such as synchronous DRAM (SDRAM) or Rambus DRAM (RDRAM), etc.), a static memory **406** (e.g., flash memory, static random access memory (SRAM), MRAM, etc.), and a secondary memory **418** (e.g., a data storage device), which communicate with each other via a bus **430**.

(34) Processor **402** represents one or more general-purpose processing devices such as a microprocessor, central processing unit, or the like. More particularly, the processor **402** may be a complex instruction set computing (CISC) microprocessor, reduced instruction set computing (RISC) microprocessor, very long instruction word (VLIW) microprocessor, processor implementing other instruction sets, or processors implementing a combination of instruction sets. Processor **402** may also be one or more special-purpose processing devices such as an application specific integrated circuit (ASIC), a field programmable gate array (FPGA), a digital signal processor (DSP), network processor, or the like. Processor **402** is configured to execute the processing logic **426** for performing the operations described herein.

(35) The computer system **400** may further include a network interface device **408**. The computer system **400** also may include a video display unit **410** (e.g., a liquid crystal display (LCD), a light emitting diode display (LED), or a cathode ray tube (CRT)), an alphanumeric input device **412** (e.g., a keyboard), a cursor control device **414** (e.g., a mouse), and a signal generation device **416** (e.g., a speaker).

(36) The secondary memory **418** may include a machine-accessible storage medium (or more specifically a computer-readable storage medium) **432** on which is stored one or more sets of instructions (e.g., software **422**) embodying any one or more of the methodologies or functions described herein. The software **422** may also reside, completely or at least partially, within the main memory **404** and/or within the processor **402** during execution thereof by the computer system **400**, the main memory **404** and the processor **402** also constituting machine-readable storage media. The software **422** may further be transmitted or received over a network **420** via the network interface

device 408.

(37) While the machine-accessible storage medium 432 is shown in an exemplary embodiment to be a single medium, the term “machine-readable storage medium” should be taken to include a single medium or multiple media (e.g., a centralized or distributed database, and/or associated caches and servers) that store the one or more sets of instructions. The term “machine-readable storage medium” shall also be taken to include any medium that is capable of storing or encoding a set of instructions for execution by the machine and that cause the machine to perform any one or more of the methodologies of the present disclosure. The term “machine-readable storage medium” shall accordingly be taken to include, but not be limited to, solid-state memories, and optical and magnetic media.

(38) In accordance with an embodiment of the present disclosure, a machine-accessible storage medium has instructions stored thereon which cause a data processing system to perform a method of developing a metal oxo photoresist on a substrate with plasma processes. The method includes exposing a metal oxo photoresist to provide exposed and unexposed regions, and placing a substrate with the exposed photoresist into a plasma chamber. In an embodiment, a gas is flown into the plasma chamber and a plasma is struck. The gas may comprise a reactive gas and an inert gas. In an embodiment, the plasma reacts with the unexposed regions of the photoresist to convert the unexposed regions of the photoresist into a volatile byproduct that can be purged from the plasma chamber. For example, the reactive gas may comprise one or more of a Cl.sub.2, Br.sub.2, HBr, HCl, and H.sub.2.

(39) Thus, methods for forming a developing a metal oxo photoresist using plasma processes have been disclosed.

Claims

1. A method of developing a metal oxo photoresist, comprising: providing a substrate with the metal oxo photoresist into a chamber, wherein the metal oxo photoresist comprises exposed regions and unexposed regions, the exposed regions comprising a first non-zero carbon concentration, and the unexposed regions comprising a second non-zero carbon concentration, and wherein the second non-zero carbon concentration of the unexposed regions is higher than the first non-zero carbon concentration of the exposed regions; flowing a gas into the chamber for a duration between 5 seconds and 120 seconds, wherein the gas reacts with the unexposed regions with a selectivity greater than 10:1 compared to the exposed regions to produce a volatile byproduct, and wherein the gas comprises a reactive gas comprising one or more of Br.sub.2 or HCl, the gas has a pressure between 5 mTorr and 20 mTorr in the chamber, the substrate has a temperature between 40° C. and 100° C., wherein the chamber is powered by a source of between 200 W and 1200 W, and a power bias between 0 W and 200 W; and etching the substrate before removing the substrate from the chamber.
2. The method of claim 1, further comprising: striking a plasma in the chamber.
3. The method of claim 1, wherein the gas further comprises an inert gas.
4. The method of claim 3, wherein a ratio of a flowrate of the inert gas to a flowrate of the reactive gas is between 0:1 and 50:1.
5. The method of claim 1, wherein reacting the gas with the unexposed regions is implemented with a thermal process without a plasma.
6. The method of claim 1, wherein the power bias is pulsed, wherein the pulsing has a duty cycle between 0% and 100%.
7. The method of claim 1, wherein the metal oxo photoresist comprises SnOC.
8. The method of claim 1, wherein the exposed regions comprise a cross-linked metal oxide network, and wherein the unexposed regions comprise a metal oxide cluster.
9. A method of developing a metal oxo photoresist, comprising: providing a substrate with the

metal oxo photoresist on a surface of the substrate; exposing the metal oxo photoresist to form exposed regions and unexposed regions, the exposed regions comprising a first non-zero carbon concentration, and the unexposed regions comprising a second non-zero carbon concentration, wherein the second non-zero carbon concentration of the unexposed regions is higher than the first non-zero carbon concentration of the exposed regions; placing the substrate in a plasma chamber; flowing a gas into the plasma chamber for a duration between 5 seconds and 120 seconds, wherein the gas reacts with the unexposed regions with a selectivity greater than 10:1 compared to the exposed regions to produce a volatile byproduct, and wherein the gas comprises a reactive gas comprising one or more of Br.sub.2 or HCl, the gas has a pressure between 5 mTorr and 20 mTorr in the chamber, the substrate has a temperature between 40° C. and 100° C., wherein the chamber is powered by a source of between 200 W and 1200 W, and a power bias between 0 W and 200 W; striking a plasma in the plasma chamber, wherein the plasma reacts with the unexposed regions to produce a volatile byproduct; purging the plasma chamber; and etching the substrate before removing the substrate from the plasma chamber.

10. The method of claim 9, wherein the gas further comprises an inert gas.

11. The method of claim 10, wherein a ratio of a flowrate of the inert gas to a flowrate of the reactive gas is between 0:1 and 50:1.

12. The method of claim 9, wherein the metal oxo photoresist comprises SnOC.

13. The method of claim 9, wherein exposing the metal oxo photoresist comprises exposing the metal oxo photoresist to extreme ultraviolet (EUV) radiation.

14. The method of claim 1, wherein the reactive gas is Br.sub.2.

15. The method of claim 1, wherein the reactive gas is HCl.

16. The method of claim 9, wherein the reactive gas is Br.sub.2.

17. The method of claim 9, wherein the reactive gas is HCl.
