

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12398278
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Miller; Cory G.

Chitosan-containing coating compositions

Abstract

Paint and coating compositions including chitosan exhibit one or more of improved elongation, improved thermocycling characteristics, reduced leaching of coating components, or lesser susceptibility to fungal and mildew defacement than conventional coatings, articles coated in the same, and methods for making said coating compositions or coated articles.

Inventors:	Miller; Cory G. (Cleveland, OH)
Applicant:	SWIMC LLC (Cleveland, OH)
Family ID:	1000008778548
Appl. No.:	18/187806
Filed:	March 22, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230303858 A1	Sep. 28, 2023

Related U.S. Application Data

continuation parent-doc WO PCT/US2021/051013 20210920 PENDING child-doc US 18187806
us-provisional-application US 62706973 20200922

Publication Classification

Int. Cl.: C09D7/65 (20180101); C08K3/22 (20060101); C08L5/08 (20060101); C09D5/02 (20060101); C09D7/20 (20180101); C09D7/40 (20180101); C09D7/61 (20180101); C09D7/80 (20180101); C09D105/08 (20060101); C09D133/04 (20060101)

U.S. Cl.:

CPC **C09D7/65** (20180101); **C08K3/22** (20130101); **C08L5/08** (20130101); **C09D5/022** (20130101); **C09D5/025** (20130101); **C09D5/028** (20130101); **C09D7/20** (20180101); **C09D7/61** (20180101); **C09D7/69** (20180101); **C09D7/80** (20180101); **C09D105/08** (20130101); **C09D133/04** (20130101); C08K2003/2241 (20130101)

Field of Classification Search

CPC: C09D (7/65); C09D (7/69); C09D (7/61); C09D (7/20); C09D (7/80); C09D (5/022); C09D (5/025); C09D (5/028); C09D (105/08); C09D (133/04); C08K (3/22); C08K (2003/2241); C08L (5/08)

USPC: 524/27

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5691014	12/1996	Andersen	N/A	N/A
6132750	12/1999	Perrier et al.	N/A	N/A
7541017	12/2008	Bringley et al.	N/A	N/A
7807194	12/2009	Modliszewski et al.	N/A	N/A
8008439	12/2010	Tsukada et al.	N/A	N/A
8287952	12/2011	Bringley et al.	N/A	N/A
9023333	12/2014	Frahling et al.	N/A	N/A
9044410	12/2014	Domard et al.	N/A	N/A
9556523	12/2016	Wasserfallen et al.	N/A	N/A
10280513	12/2018	Wasserfallen et al.	N/A	N/A
10377878	12/2018	Li et al.	N/A	N/A
2005/0014851	12/2004	Bringley	N/A	N/A
2007/0272119	12/2006	Ichinose et al.	N/A	N/A
2010/0016443	12/2009	Toledano et al.	N/A	N/A
2011/0009268	12/2010	Uhr et al.	N/A	N/A
2013/0145957	12/2012	Shchukin et al.	N/A	N/A
2013/0165525	12/2012	Scheuing et al.	N/A	N/A
2015/0179357	12/2014	Ichinomiya et al.	N/A	N/A
2015/0322288	12/2014	Wasserfallen et al.	N/A	N/A
2016/0296665	12/2015	Ingber et al.	N/A	N/A
2016/0376535	12/2015	Chieffi et al.	N/A	N/A
2017/0066009	12/2016	Bremser et al.	N/A	N/A
2017/0081542	12/2016	Bremser et al.	N/A	N/A
2017/0189928	12/2016	Scharrenbach	N/A	N/A
2017/0369640	12/2016	Burgo et al.	N/A	N/A
2018/0207912	12/2017	Li et al.	N/A	N/A
2019/0000745	12/2018	Chiattello et al.	N/A	N/A
2019/0048207	12/2018	Wasserfallen et al.	N/A	N/A
2019/0155975	12/2018	Cetti et al.	N/A	N/A
2020/0255631	12/2019	Prinyawiwatkul et al.	N/A	N/A
2020/0276057	12/2019	Salmon et al.	N/A	N/A
2021/0108162	12/2020	Scheuing et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1139116	12/1996	CN	N/A
1712431	12/2004	CN	N/A
101190976	12/2007	CN	N/A
100448921	12/2008	CN	N/A
101347127	12/2008	CN	N/A
101314631	12/2010	CN	N/A
101864051	12/2010	CN	N/A
101314650	12/2011	CN	N/A
102417778	12/2011	CN	N/A
101717529	12/2011	CN	N/A
102816493	12/2011	CN	N/A
103058945	12/2012	CN	N/A
102492335	12/2012	CN	N/A
103628306	12/2013	CN	N/A
103756481	12/2013	CN	N/A
102775647	12/2013	CN	N/A
103408946	12/2013	CN	N/A
103194134	12/2014	CN	N/A
103146264	12/2014	CN	N/A
104530843	12/2014	CN	N/A
104628888	12/2014	CN	N/A
103232619	12/2014	CN	N/A
104774244	12/2014	CN	N/A
104830074	12/2014	CN	N/A
104927491	12/2014	CN	N/A
105017913	12/2014	CN	N/A
103467623	12/2014	CN	N/A
105462496	12/2015	CN	N/A
105544302	12/2015	CN	N/A
105567037	12/2015	CN	N/A
105801890	12/2015	CN	N/A
105949900	12/2015	CN	N/A
106010050	12/2015	CN	N/A
106221502	12/2015	CN	N/A
106336741	12/2016	CN	N/A
106381017	12/2016	CN	N/A
106497291	12/2016	CN	N/A
106832439	12/2016	CN	N/A
106691029	12/2016	CN	N/A
106820812	12/2016	CN	N/A
106867344	12/2016	CN	N/A
107509808	12/2016	CN	N/A
107119491	12/2016	CN	N/A
107141370	12/2016	CN	N/A
107254270	12/2016	CN	N/A
107312285	12/2016	CN	N/A
107353716	12/2016	CN	N/A

107384133	12/2016	CN	N/A
107474611	12/2016	CN	N/A
107502071	12/2016	CN	N/A
107739556	12/2017	CN	N/A
107936766	12/2017	CN	N/A
107981475	12/2017	CN	N/A
108102489	12/2017	CN	N/A
108102544	12/2017	CN	N/A
108192122	12/2017	CN	N/A
108192154	12/2017	CN	N/A
108219212	12/2017	CN	N/A
106987234	12/2017	CN	N/A
108250475	12/2017	CN	N/A
108310471	12/2017	CN	N/A
108329788	12/2017	CN	N/A
108342132	12/2017	CN	N/A
107793855	12/2017	CN	N/A
108384064	12/2017	CN	N/A
108478494	12/2017	CN	N/A
108530667	12/2017	CN	N/A
108586828	12/2017	CN	N/A
105002780	12/2017	CN	N/A
108610539	12/2017	CN	N/A
108624049	12/2017	CN	N/A
108753030	12/2017	CN	N/A
108892810	12/2017	CN	N/A
109054105	12/2017	CN	N/A
109054621	12/2017	CN	N/A
109082165	12/2017	CN	N/A
109135449	12/2018	CN	N/A
109206951	12/2018	CN	N/A
109206986	12/2018	CN	N/A
109232943	12/2018	CN	N/A
109233730	12/2018	CN	N/A
109294001	12/2018	CN	N/A
109354955	12/2018	CN	N/A
109370351	12/2018	CN	N/A
109810526	12/2018	CN	N/A
109825145	12/2018	CN	N/A
109942208	12/2018	CN	N/A
110028863	12/2018	CN	N/A
110105531	12/2018	CN	N/A
4303415	12/1993	DE	N/A
1919981	12/2007	EP	N/A
3170394	12/2016	EP	N/A
3247756	12/2016	EP	N/A
3922689	12/2020	EP	N/A
2001342435	12/2000	JP	N/A
2003174169	12/2002	JP	N/A
2003306646	12/2002	JP	N/A

2007169610	12/2006	JP	N/A
2007320977	12/2006	JP	N/A
101765374	12/2016	KR	N/A
101889286	12/2017	KR	N/A
I257346	12/2005	TW	N/A
200509603	12/2004	WO	N/A
2020234643	12/2019	WO	N/A

OTHER PUBLICATIONS

ProQuip, Inc., “Viscosity Conversion Chart” (www.proquipinc.com/viscosity_conversion_chart) (Year: 2010). cited by examiner

International Search Report for PCT/US2021/051013 dated Dec. 21, 2021, 7 pages. cited by applicant

Eikenes, et al. “Chitosan for wood protection—state of the art” The International Research Group on Wood Protection, 36th Annual Meeting, Bangalore, India, Apr. 24-28, 2005. cited by applicant
 Piegat, et al. “The Importance of Reaction Conditions on the Chemical Structure of N,O-Acylated Chitosan Derivatives”, *Molecules* 2019, 24, 3047; doi:10.3390/molecules24173047, 16 pages. cited by applicant

Extended European Search Report for European Patent Application No. 21873239.4 dated Oct. 2, 2024. cited by applicant

Primary Examiner: Cho; Ling Siu

Assistant Examiner: Grinsted; Ronald

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS (1) This application claims priority to and is a continuation of International Patent Application No. PCT/US2021/051013 filed on Sep. 20, 2021, which claims priority to U.S. provisional patent application No. 62/706,973, filed on Sep. 22, 2020.

FIELD OF THE INVENTION

(1) This invention relates to paints and coatings containing chitosan that provide useful benefits over conventional coatings in the form of improved resistance to leaching, improved elongation and lesser susceptibility to fungal or mildew defacement than conventional coatings, articles coated in the same, and methods for making said coatings or coated articles.

BACKGROUND

(2) Paints and coatings typically contain three essential ingredients: carrier liquid, binder, and additives. Pigment is also commonly added in many paints and coatings. Each of such ingredients may comprise a single component or several different items mixed into the paint or coating.

(3) The carrier liquid is a fluid component of the paint which serves to carry all of the other paint components. The carrier liquid is part of the wet paint and usually evaporates as the paint forms a film and dries on a surface. In latex paints, the carrier liquid is usually water. In oil-based paints, the carrier liquid is usually an organic solvent. The amount and type of liquid is usually determined by features of the other paint components.

(4) The binder component of a paint or coating is what causes the paint or coating to form a film on and adhere to a surface. In a latex paint, the binder comprises a latex resin, usually selected from acrylics, vinyl acrylics, styrene acrylics, or polyurethane dispersions (“PUDs”). In a latex paint or

coating, the latex resin particles usually are in a dispersion with water as the carrier liquid.

(5) Pigments provide the paint or coating with both decorative and protective features. Pigments are solid particles used to provide the paint or coating with various qualities, including but not limited to color, opacity, and durability. The paint or coating may also contain other solid particles such as polyurethane beads or other solids. Pigments and other solids add bulk to the paint or coating and their levels are related to the gloss or flatness of the paint or coating. Pigments may also impart color to a paint or coating.

(6) A multitude of additives may be included in paints and coatings. The additives are typically used at relatively low levels in the paint/coating formulation, but contribute to various properties of paints and coatings, including rheology, stability, paint performance, in-can preservation, dry film preservation or protection, and application quality.

(7) Biocides are additives that have antimildew, bacteriostatic and bactericidal properties. A variety of biocidal agents are well known and are used for various purposes including but not limited to preservation of wet paint or coatings (“in-can” preservation) and preservation or protection of dry films on coated articles. Such biocides include inorganic biocidal agents, for example, those containing metal ions, such as silver, zinc, and copper. Other inorganic biocides include phosphates, metal ion, metal or other biocide containing zeolites or hydroxyapatites. There are also organic biocides including organic acids, phenols, alcohols, and quaternary ammonium compounds.

(8) Some biocides act specifically, such as mildewcidal or fungicidal agents, which are additives that have mildewcidal or fungicidal properties. Mildewcidal and fungicidal agents work to prevent, reduce, or forestall the formation of mildew in cured paint or coating films. Zinc compounds, including zinc oxide, are common fungicides and mildewcides, the use of which is effective at mildew, mold, and fungus prevention and/or reduction in cured films. Zinc oxide can have drawbacks and create issues in dispersibility of paints and coatings. Other known fungicides include iodopropynyl butylcarbamate (IPBC), 2-octyl-3 (2H)-isothiazolone (OIT), chlorothalonil, and the like.

(9) Chitosan is a bio-based material that may be obtained in a renewable fashion from chitin coming from crustaceans, among other sources, and, if dispersible, would be a useful additive or filler in paint formulations. In conventional practice, despite its relatively low cost and relative renewability, chitosan is not used in paints and coatings due to its water insolubility, a negative effect on the quality of the paint and coatings, and the difficulty in adequately dispersing chitosan in latex and other waterborne, dispersion systems for paints and coatings. Providing a consistently dispersed paint or coating is important for ease of manufacturability but also for providing a high-quality paint without grit or other defects in consistency, application, appearance, or feel.

(10) The relevant art has pursued alternative approaches in attempts at solubilizing or dispersing chitosan in water. One such approach involves providing chitosan in acidic solution. Acidic solutions are highly impractical for direct addition to waterborne paints and coatings, which are overwhelmingly basic in pH. Adding a significantly acidic solution to maintain acidity and thus maintain the chitosan in solution would greatly disturb the stability of a coating formulation and would require drastic reformulation. Other approaches require cost-prohibitive chemical modification to the chitosan polymer backbone with hydrophilic groups prior to addition to waterborne paints or coatings to provide water solubility.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1A shows a Hegman gauge drawdown of Positive Control Paint 1; FIG. 1B shows a Hegman gauge drawdown of Example Paint 1.

(2) FIG. 2A shows a microscopic image of a drawdown of Positive Control Paint 1; FIG. 2B shows a microscopic image of a drawdown of Example Paint 1.

(3) FIG. 3A, FIG. 3B, FIG. 3C, FIG. 3D, and FIG. 3E show Hardie boards painted with the following paints after 19 weeks in a 90° F., 95-98% relative humidity mildew chamber. FIG. 3A shows a Hardie Board painted with Positive Control Paint 1; FIG. 3B shows a Hardie board painted with Negative Control Paint; FIG. 3C shows a Hardie board painted with Example Paint 1; FIG. 3D shows a Hardie Board painted with Example Paint 2; and FIG. 3E shows a Hardie board painted with Example Paint 3.

(4) FIG. 4A, FIG. 4B, FIG. 4C, FIG. 4D, and FIG. 4E show the following paints applied to aluminum panels after 19 weeks in a 90° F., 95-98% relative humidity mildew chamber. FIG. 4A shows aluminum panel painted with Positive Control Paint 1; FIG. 4B shows aluminum panel painted with Negative Control Paint; FIG. 4C shows aluminum panel painted with Example Paint 1; FIG. 4D shows aluminum panel painted with Example Paint 2; and FIG. 3E shows aluminum panel painted with Example Paint 3.

(5) FIG. 5A, FIG. 5B, and FIG. 5C show images of drawdowns of the following paints on Whitman filter paper, after inoculation with an algae mixture and 3 weeks incubation per ASTM D5589-19. FIG. 5A shows Positive Control Paint 1, FIG. 5B shows Negative Control Paint, and FIG. 5C shows Example Paint 1.

(6) FIG. 6A is an illustration of incorporation of an acidic chitosan solution into a paint or coating during the grind stage, to yield a neutralized chitosan dispersion following slow addition of ammonia. FIG. 6B illustrates the subsequent addition of the remainder of mill-based ingredients.

SUMMARY OF THE INVENTION

(7) The present invention comprises, in one embodiment, a paint or coating composition comprising water, latex binder resin, and additives, wherein such additives include, but are not limited to, a chitosan compound. In some embodiments, the chitosan compound additive has a particle size of less than 30 microns in the paint or coating, determined using ASTM D1210-05 "Standard Test Method for Fineness of Dispersion of Pigment-Vehicle Systems by Hegman-Type Gage". In another embodiment, the invention comprises a coated article formed from a paint or coating composition comprising water, latex binder resin, and additives, wherein such additives include but are not limited to, a chitosan compound and wherein the paint or coating composition dries to form a film on the coated article. The chitosan compound is distributed throughout the film on the coated article. In some embodiments, the chitosan compound additive has as particle size less than 30 microns when dispersed in a paint or coating, determined using ASTM D1210-05. Hegman gauge values below 30 microns are also indicative of adequate dispersibility of the chitosan. The dried paint or coating film displays improved elongation as measured according to ASTM D2370-16 "Standard Test Method for Tensile Properties", improved thermocycling characteristics using the rating scales according to ASTM D714-02 "Standard Test Method for Evaluating Degree of Blistering of Paints" and ASTM D661-93 "Standard Test Method for Evaluating Degree of Cracking of Exterior Paints", improved resistance to surfactant or other additive leaching as measured according to methods described herein. A modified version of the ASTM D5589-19 method "Standard Test Method for Determining the Resistance of Paint Films and Related Coatings to Algal Defacement" can be used to show reduced leaching of paint components in the exemplary compositions. The dried film may also be less susceptible to mildew or fungal growth and defacement than identical paints or coatings that do not include the chitosan compound. In some embodiments, coatings containing the chitosan compound may require reduced amounts of traditional fungicides like zinc oxide.

(8) In embodiments of the present invention, chitosan is incorporated into said paints and coatings, wherein the chitosan ranges in particle size in said paints and coatings from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm .

(9) In further useful embodiments of the present invention, chitosan is incorporated into said

coatings from 0.02 to 1.0, 0.02 to 0.75, 0.05 to 0.40, or 0.02 to 0.30 percent by weight of dry coating solids.

(10) In another embodiment, the paint or coating composition of the present invention may also include a pigment and extenders or fillers. The paint or coating composition of this embodiment has one or more of the following characteristics: pigment volume concentration (PVC) of less than 60, about 25% to about 65% by weight solids, at least 17% by weight binder polymer solids up to about 55% by weight binder polymer solids, and at least 10% by weight of a hiding pigment, for example, titanium dioxide. Further, the paint or coating composition may have one or more of the following qualities: improved dispersion of chitosan with chitosan particles in the paint or coating having particle size from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm and being evenly distributed, improved elongation in dried film form, improved thermocycling characteristics, improved resistance to surfactant or other additive leaching, and less susceptibility to fungal defacement in dried film form.

(11) In further embodiments, said coating includes biocide additives. Such biocide additives may be selected by one having skill in the art to provide adequate additional mildew or fungal protection or other biocidal function, including but not limited to in-can preservation or dry film preservation.

(12) In another embodiment of the invention, a method of manufacture is provided whereby a coating is made, the coating comprising water, latex binder resin, and additives, wherein such additives include, but are not limited to, a chitosan compound. The added chitosan is of relatively small particle size, in some embodiments less than 200 μm and others 100 μm . In certain other embodiments, a small particle size chitosan is obtained from traditional sources of chitosan by applying high rates of shear (e.g., as applied to pigment in the pigment grind stage of paint making) to an aqueous acetic acid solution containing chitosan and adding base (e.g. ammonium hydroxide) to neutralize the solution and precipitate out the chitosan from solution. In certain embodiments of the method of manufacture, the coating further comprises a pigment, and the chitosan is incorporated into the coating during the pigment grind stage. In certain embodiments of the method, the coating is further coated on an article and allowed to dry. The wet coating has a pH above 7, while the dry coating has a pH below 7, in certain embodiments from 5 to 6. The deacetylated, primary amine of the chitosan is present in the film in its protonated state.

DETAILED DESCRIPTION OF THE INVENTION

(13) The present invention comprises, in one embodiment, a paint or coating composition comprising water, latex binder resin, and additives, wherein such additives include, but are not limited to, a chitosan compound. In some embodiments, the chitosan compound additive has a particle size of less than 30 microns in the paint or coating, determined using ASTM D1210-05 "Standard Test Method for Fineness of Dispersion of Pigment-Vehicle Systems by Hegman-Type Gage". In another embodiment, the invention comprises a coated article formed from a paint or coating composition comprising water, latex binder resin, and additives, wherein such additives include but are not limited to, a chitosan compound and wherein the paint or coating composition dries to form a film on the coated article. The chitosan compound is distributed throughout the film on the coated article. In some embodiments, the chitosan compound additive has as particle size less than 30 microns when dispersed in a paint or coating, determined using ASTM D1210-05. Hegman gauge values below 30 microns are also indicative of adequate dispersibility of the chitosan. The dried paint or coating film displays improved elongation as measured according to ASTM D2370-16 "Standard Test Method for Tensile Properties", improved thermocycling characteristics using the rating scales according to ASTM D714-02 "Standard Test Method for Evaluating Degree of Blistering of Paints" and ASTM D661-93 "Standard Test Method for Evaluating Degree of Cracking of Exterior Paints", improved resistance to surfactant or other additive leaching as measured according to methods described herein. A modified version of the ASTM D5589-19 method "Standard Test Method for Determining the Resistance of Paint Films

and Related Coatings to Algal Defacement” can be used to show reduced leaching of paint components in the exemplary compositions. The dried film may also be less susceptible to mildew or fungal growth and defacement than identical paints or coatings that do not include the chitosan compound. In some embodiments, coatings containing the chitosan compound may require reduced amounts of traditional fungicides like zinc oxide.

(14) In embodiments of the present invention, chitosan is incorporated into said paints and coatings, wherein the chitosan ranges in particle size in said paints and coatings from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm .

(15) In further useful embodiments of the present invention, chitosan is incorporated into said coatings from 0.02 to 1.0, 0.02 to 0.75, 0.05 to 0.40, or 0.02 to 0.30 percent by weight of dry coating solids.

(16) In another embodiment, the paint or coating composition of the present invention may also include a pigment and extenders or fillers. The paint or coating composition of this embodiment has one or more of the following characteristics: pigment volume concentration (PVC) of less than 60, about 25% to about 65% by weight solids, at least 17% by weight binder polymer solids up to about 55% by weight binder polymer solids, and at least 10% by weight of a hiding pigment, for example, titanium dioxide. Further, the paint or coating composition may have one or more of the following qualities: improved dispersion of chitosan with chitosan particles in the paint or coating having particle size from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm and being evenly distributed, improved elongation in dried film form, improved thermocycling characteristics, improved resistance to surfactant or other additive leaching, and less susceptibility to fungal defacement in dried film form.

(17) In further embodiments, said coating includes biocides additives. Such biocide additives may be selected by one having skill in the art to provide adequate additional mildew or fungal protection or other biocidal function, including but not limited to in-can preservation or dry film preservation.

(18) In another embodiment of the invention, a method of manufacture is provided whereby a coating is made, the coating comprising water, latex binder resin, and additives, wherein such additives include, but are not limited to, a chitosan compound. The added chitosan is of relatively small particle size, in some embodiments less than 200 μm and others 100 μm . In certain other embodiments, a small particle size chitosan is obtained from traditional sources of chitosan by applying high rates of shear (e.g., as applied to pigment in the pigment grind stage of paint making) to an aqueous acetic acid solution containing chitosan and adding base (e.g. ammonium hydroxide) to neutralize the solution and precipitate out the chitosan from solution. In certain embodiments of the method of manufacture, the coating further comprises a pigment, and the chitosan is incorporated into the coating during the pigment grind stage. In certain embodiments of the method, the coating is further coated on an article and allowed to dry. The wet coating has a pH above 7, while the dry coating has a pH below 7, in certain embodiments from 5 to 6. The deacetylated, primary amine of the chitosan is present in the film in its protonated state.

(19) Chitosan Additive

(20) The term “chitosan” as used herein refers to derivatives of naturally occurring chitin having the following general chemical structure:

(21) ##STR00001## wherein n indicates the number of repeating structural units in a polymeric or oligomeric structure. Minor chemical variations in this structure are possible and will be recognized by persons having skill in the art. Chitosan may also be obtainable from other sources recognized by those having skill in the art.

(22) Chitosan is obtainable from a number of sources by deacetylation of naturally occurring chitin. Exemplary sources of chitosan are available in different molecular weights, and ordinarily provided in acidic solution from Tidal Vision Inc. located in Bellingham, WA, Millipore Sigma, a subsidiary

of Merk KGaA headquartered in Burlington, VT, Qingdao Yunzhou Biochemistry Co. Ltd. Qingdao, China, KitoZyme LLC (providing vegan-sourced chitosan) located in Herstal, Belgium, and Kimica Corporation located in Chuo-ku. Chitosan can be obtained in a dry flake form, in acidic solution, or other form. Varying molecular weights of chitosan are useful for the present invention, including but not limited to commonly available molecular weights.

(23) Particle size of conventionally available sources of chitosan and those used in the relevant art range are commonly above 60 microns when added to paint or coatings formulations as measured by Hegman gauge drawdown. These relatively large particle sizes result in gritty appearing, poorly applying paints or coatings that are unacceptable for commercial application. Additionally, larger particles have less available surface area per equivalent mass for interaction with other components of the paint.

(24) In embodiments of the present invention, Chitosan compounds added to paints or coatings of the present invention are of particle size from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm as measured by Hegman gauge drawdown. Without being bound by theory, it is believed that the smaller particle size of the chitosan in the paints and coatings of the present invention and resulting greater surface area per equivalent mass allows for greater interaction with components like surfactants, potentially resulting in less leaching of coating materials. One specific theorized interaction could be hydrogen bonding occurring between the chitosan and any polar monomers in the binder polymer of a paint or coating, perhaps allowing for additional positive properties like improved elongation and thermocycling.

(25) In embodiments of the present invention, chitosan is believed to act in one sense analogously to a filler or extender particle. Extenders or fillers may be used to reduce the quantity of the pigment required to achieve a desired hiding ability, sheen, etc., without significantly affecting the color of a paint or coating established by the pigment. Exemplary, conventional fillers include, for example, sodium-potassium alumina silicates such as MINEX® 4 and MINEX® 10 (sold by Unimin Corporation). When used, such fillers may be employed in any desired amount.

(26) Paint and Coatings Compositions and Methods of Preparations of Same

(27) A paint or coating composition made in accordance with the present invention may comprise chitosan in amounts from about 0.02 to 1.0, 0.02 to 0.75, 0.05 to 0.40, or 0.02 to 0.30 percent by weight of dry coating solids. Persons having skill in the art, in light of this disclosure, will appreciate that the amount of chitosan that can be added to a paint or coating formulation will vary based on the amount of other pigments or fillers/extendors in the paint or coating, which is indicated by the coating's base designation and/or sheen. In an ultradeep coating, for example, additional chitosan, which behaves like a filler when properly dispersed in a paint or coating formulation, could be added, perhaps in greater amounts than the ranges provided above. The maximum amount of chitosan that can be added to a paint or coatings formulation, like with other extendors or fillers, is bounded by an increasing viscosity when a threshold amount of chitosan is added.

(28) Paint or coating compositions in accordance with the present invention generally comprise at least about 17%, for example, at least about 17.5% by weight, to about 55% by weight of binder polymer solids. Binders useful in latex paint compositions are known in the art and include polymeric binders, such as acrylics, vinyl acrylics, or styrene acrylics binders. Other binder suitable for waterborne paint and coatings formulations may also be used and include but are not limited to polyurethane dispersions, waterborne alkyds, and mixtures or modifications thereof. In one embodiment of the present invention, the paint or coating composition is formulated to have a binder that does not result in precipitation of components or the formation of grit. The paint and coatings compositions of the present invention may further comprise at least about 5% by weight pigments. Such pigments may comprise inorganic pigments, such as titanium dioxide. Exemplary paint and coatings compositions comprise at least about 11% by weight, further for example, at

least about 12% by weight, further for example, at least about 13% by weight, further for example, at least about 14% by weight, further for example at least about 15% by weight, further for example, at least about 16%, further for example at least about 17%, further for example, at least about 18%, further for example at least about 19%, and even further for example at least about 20% up to about 30% by weight titanium dioxide. In another useful embodiment, the paint or coating composition comprises more than 10% titanium dioxide. Other colored pigments or dyes may also be added to the paint, alone or in combination, to produce a wide range of colored paint. Suitable additional pigments may include calcium carbonate, talc, clay, silicates, aluminum silicates, calcium metasilicates, aluminum potassium silicates, magnesium silicates, barium sulfates, nepheline syenite, feldspar, zinc oxides or sulfides, or others known to those skilled in the art. Such additional colored pigments may be included in amounts up to about 30% by weight, for example, about 10% to about 20%. In some cases, "pigments" may also refer to functional fillers which are non-water-soluble solids. Such functional fillers may include solids which provide additional functional characteristics to the paint, for example, intumescent ingredients, such as ammonium polyphosphates, melamines, pentaerythritol and similar compounds. In one useful embodiment, the coating composition of the present invention is substantially free or totally free of intumescent ingredients such as ammonium polyphosphates, melamines, and pentaerythritol and similar compounds. In further embodiments, paints and coatings comprise no or substantially no pigment and are considered "clear coats" for application to various substrates.

(29) The pigment volume concentration, or PVC, of a coating is the ratio of the volume of pigments (including functional fillers and fillers or extenders) to the volume of total non-volatile material (i.e. pigment and binder) present in the coating. The coating of the present invention preferably has a PVC of about 5 to about 60. In addition, the coating composition of the present invention has a maximum solids content of less than 65% by weight, for example, about 25% by weight to about 60% by weight, further for example about 30% by weight to about 58% by weight. In certain embodiments, the PVC of the present invention can be zero.

(30) The paints and coatings disclosed herein may also include various other additives, including but not limited to thickeners, such as urethane thickeners, and acrylic thickeners in amounts up to about 10% by weight, for example about 1% to about 2%. Synthetic organic materials might also be incorporated; these include plastic beads, hollow spheres or other similar materials. Other optional components include glycols such as ethylene and/or propylene glycol in amounts up to about 7% and other solvents such as diethylene glycol dibenzoate and dipropylene glycol dibenzoate in amounts up to about 3%. The coating composition may also contain pigment dispersing agents which can be solvents or surfactants; wet paint preservatives; dry film preservatives; foam control agents such as oils, fatty acids and silicones; slip and mar additives; adhesion promoters, and/or other known paint additives.

(31) The paint or coating composition of the present invention may also comprise biocides including but not limited to metal ion containing compounds, polymeric biocides, heterocyclic compounds, phenols, organometallics, aldehydes, proteins, peroxygens, alcohols, enzymes, polypeptides, cationic surfactants (including quaternary ammonium compounds), and halogen releasing compounds.

(32) Paints and coatings made in accordance with the present invention are generally formulated to have a pH between 7 and 11 in the wet state ("in-can" prior to application and curing on a substrate). In exemplary embodiments, the wet state pH is from 8-10, or in other embodiments, 9-10. Various pH modifiers can be used to regulate wet-state pH. The pH of a paint or coating is very important to provide for dispersibility and compatibility of all of the other components conventionally used in paint and coatings making. Conventional methods of incorporating chitosan into a coating involve providing the coating as an acidic solution, having a significantly lower pH in the wet state that is friendly to the dissolving of chitosan in the wet-state coating. The present invention involves the dispersion of chitosan in a traditional, higher pH wet-state coating, which

allows formulation with otherwise conventional materials; a formulation toolbox that is convenient and cost-effective for a paint and coating formulator.

(33) It should be noted that in order to make a waterborne paint or coating formulation, an appropriate dispersant/surfactant system is needed in order to disperse the polymer and pigments in the paint or coatings formulation. The process for selecting dispersants/surfactants for paint and coatings formulations is well known to those of ordinary skill in the paint formulation art. One of ordinary skill in the art would be able to select a dispersant/surfactant combination in order to make a desired paint or coating composition having good stability characteristics.

(34) Method of Preparing a Coating Composition

(35) The invention encompasses in some embodiments a method for preparing a coating composition. Generally, a method of making a coating composition can comprise conventional manufacturing methods for forming a paint or coating and then the addition of the chitosan compound. Conventional manufacturing processes often involve four or more stages, these including pre-thin stage, a grind stage, a wash stage, and a thindown or letdown stage. In the pre-thin stage, one or more binder resins may be blended together with a carrier liquid within a thindown tank. Low-shear mixing may be applied in the thindown tank to form a pre-thin mixture. In the grind stage, pigments and other additives that will not homogenize under low-shear mixing may be dispersed into a carrier liquid under high shear conditions. The grind stage may be carried out in a high-shear mixing device, such as mill. The high shear applied in the grind stage breaks up agglomerates of particles and wet particles with a liquid. The composition of the liquid added when thinning the grind may be the same as or different from the composition of the carrier liquid used when preparing the grind. Next, in a wash stage, a wash liquid, which may have a composition that is the same as or different from the composition of the carrier liquid, may be pumped into the high-shear mixing device to move the grind paste into the thindown tank. Finally, in a thindown stage, the grind paste, the carrier liquid, the wash liquid, and the pre-thin mixture including any other additional additives may be blended together in the thindown tank under low shear conditions. In this stage, the coating composition concentrate may be further let down through further addition of liquid, which may have the same composition as or a different composition from the carrier liquid. The method may employ these conventional stages, or the coating composition may be prepared by other suitable methods. For example, the method may employ continuous manufacturing using component slurries.

(36) One or more additives may be added at any suitable point during the manufacturing process, such as during the pre-thin stage, a grind stage, a wash stage, and a thindown or letdown stage.

(37) The chitosan compound can be added in acidic-aqueous or other solution to the paint or coating and then neutralized by the addition of a base to precipitate the chitosan into dispersion in the paint or coating. The chitosan must be added such that it is present and dispersed in the paint or coating at a particle size from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm . In preferred embodiments, application of shear such as that used in a pigment grind phase of paint-making adequately maintains a stable dispersion of the precipitated chitosan to and allows for chitosan in the paint with particle sizes of from 2 to 30 μm , 2 to 25 μm , 2 to 16 μm , or 4 to 16 μm , or less than 30 μm , less than 25 μm , less than 20 μm , or less than 16 μm . In certain embodiments, chitosan is added to the pigment grind fluid during the pigment grind stage. In preferred embodiments, the chitosan compound, prior to being added to the grind fluid is dissolved in an acetic or other acid solution. A chitosan-in-acidic solution may also be provided directly (e.g. High Molecular Weight Chitosan Acetate Aqueous Solution with 3% chitosan and 6% acetic acid by weight available from Tidal Vision Inc.). Once the chitosan acidic solution is incorporated into the grind water by pouring or any suitable addition method, the chitosan is precipitated into the grind water by the addition of base (for example, ammonia) forming a dispersion of the chitosan with the other grind fluid components. In certain embodiments, the chitosan acidic solution may be added to the grind water before any other grind

fluid components are added. In certain embodiments, the chitosan acidic solution is added alongside or after the other grind components are added. In certain embodiments, the base is added slowly, under the shear of the pigment grind stage to allow for adequate mixing and to avoid rapid or localized precipitation of the chitosan. The dispersion is maintained throughout the paint or coating-making process and the chitosan remains in stable dispersion. FIGS. 6A and 6B illustrate part of this embodiment whereby the chitosan compound is incorporated into a paint or coating during the grind stage starting in a chitosan acetate aqueous solution. An exemplary chitosan-acid aqueous solution is the “High Molecular Weight” Chitosan Acetate Aqueous Solution (3% chitosan by mass, 6% acetic acid by mass) available from Tidal Vision Inc.

(38) Once prepared, the coating composition may be dispensed into a storage container, such as a paint can. The coating composition then may be transported and stored, such as in a warehouse or on a store shelf.

(39) Coated Article with Dried Paint Film and Methods for Providing a Coated Article

(40) In certain embodiments, an article is coated with the above-described paints and coatings containing the chitosan compound such that the coating forms a dried film on the article. The dried coating film displays superior properties over an identical dried film that does not contain the chitosan compound. One such improved set of properties is in elongation. Films of the present invention may show elongation improvements from 10% additional elongation to 50% additional elongation, 10% to 40%, 20% to 50%, or 15% to 35% as compared to identical films that do not contain chitosan and as measured according to ASTM D2370-16. Without being bound to theory, it is believed that hydrogen bonding may occur between the chitosan compound and any polar monomers in the binder polymer of a paint or coating to enable improved elongation. Binder polymers with increasingly polar monomers or an increased amount of polar monomers may exhibit increased elongation.

(41) Dried films also show improved resistance to leaching of materials. Resistance to leaching is indicated by testing conducted using ASTM D5589-19, which traditionally is used to show resistance to algal defacement, but in the present case can be used to show reduced leaching by the absence of a ring of inhibition on exemplary samples. Dried films further appear to be less susceptible to fungal (including mildew) defacement than identical films not containing a chitosan compound. Susceptibility to mildew or fungal defacement can be determined using the method described in the Examples below or by any method acceptable to a person having ordinary skill in the art.

(42) The coating composition may be employed for any suitable purpose. In some embodiments, the coating composition may be applied to interior or exterior architectural surfaces such as wood, drywall, masonry, metal, and plaster, or over a primer coating. In certain embodiments, the coating composition may be applied to metals, composites, and other materials as a protective coating. In other embodiments, the coating composition may be applied to a surface to impart dry-erase characteristics. For example, the surface may be a wall, which may have paint or a primer already applied to the surface of the wall, over which the coating can be applied to form a dry-erase surface. The coating composition may be applied with brush, roller, sponge, or spray gun, or other conventional painting or coating tool. The cured coating may have any suitable thickness, such as a thickness ranging from 0.05-2 mm with preferred thickness around 0.1 mm.

Embodiments

(43) Certain embodiments of the present invention include:

(44) Embodiment 1: A coating composition comprising: (a) a carrier liquid; (c) a binder polymer; and (d) a chitosan compound having a particle size in the coating composition of less than 30 μm .

(45) Embodiment 2: The coating composition of embodiment 1, wherein the carrier liquid comprises water.

(46) Embodiment 3: The coating composition of any of embodiments 1-2, wherein the coating composition further comprises pigment.

- (47) Embodiment 4: The coating composition of any of embodiments 1-3, wherein the coating composition comprises 13% to 30% by weight pigment and the pigment is titanium dioxide.
- (48) Embodiment 5: The coating composition of any of embodiments 1-4, wherein the coating composition has a PVC below 60.
- (49) Embodiment 6: The coating composition of any of embodiments 1-5, wherein the coating composition has about 25% to about 65% by weight solids.
- (50) Embodiment 7: The coating composition of any of embodiments 1-6, wherein the coating composition has about 30% to about 60% by weight solids.
- (51) Embodiment 8: The coating composition of any of embodiments 1-7, wherein the coating composition comprises about 0.02% to about 1.0% by weight chitosan compound.
- (52) Embodiment 9: The coating composition of any of embodiments 1-8, wherein the chitosan compound has a particle size of less than 16 microns in the coating composition.
- (53) Embodiment 10: The coating composition of any of embodiments 1-9, wherein the dried paint film has a Hegman gauge rating of 5 or higher.
- (54) Embodiment 11: The coating composition of any of embodiments 1-10, wherein the paint has a viscosity under 120 KU.
- (55) Embodiment 12: A coated article, coated in the coating composition of any of embodiments 1-11.
- (56) Embodiment 13: The coated article of embodiment 12, wherein the coating composition forms a dried film on the article, and the dried film exhibits improved elongation as measured by ASTM D2370-16 and compared to an identical dried film having no chitosan compound.
- (57) Embodiment 14: The coated article of embodiments 12 or 13, wherein the coating composition forms a dried film on the article, and the dried film exhibits improved thermocycling properties as measured by ASTM D714-02 and ASTM D661-93 and compared to an identical dried film having no chitosan compound.
- (58) Embodiment 15: The coated article of any of embodiments 12-14, wherein the coating composition forms a dried film on the article, and the dried film exhibits resistance to leaching compared to an identical dried film having no chitosan compound.
- (59) Embodiment 16: The coated article of any of embodiments 12-15, wherein the coating composition forms a dried film on the article, and the dried film exhibits reduced susceptibility to mildew or fungal defacement as compared to an identical dried film having no chitosan compound.
- (60) Embodiment 17: A method of making a coating composition, the method comprising providing the coating composition of any of embodiments 1-11.
- (61) Embodiment 18: A method of making a coating composition, the method comprising: (a) providing a coating composition comprising a carrier liquid, binder polymer, and a pigment, wherein said coating composition is formed by conventional manufacturing methods comprising a grind process and a thindown process; and (b) adding a chitosan compound to the coating composition during the pigment grind process and applying shear to the chitosan compound along with the grind fluid in the course of the grind process.
- (62) Embodiment 19: The method of embodiment 18, wherein the chitosan compound is provided in step (b) in an acetic acid and water solution, and the grind process further comprises the addition of a base to neutralize and precipitate the chitosan compound from the acetic acid and water solution while shear is applied in the grind process.

EXAMPLES

Comparative and Example Paint Compositions

(63) Comparative (or “Control”) and Example paint compositions were prepared according to the weight percent amounts shown in TABLE 1, below.

(64) TABLE-US-00001 TABLE 1 Weight % in Paint Positive Positive Negative Control Control Control Example Example Example Component Paint 1 Paint 2 Paint 1 Paint 2 Paint 3 THIN-DOWN Proprietary, All 47 52.18 50 49 48.6 48.5 STAGE Acrylic Latex COMPONENTS (50%

Example Paint 1. Positive Control Paint 2 shows chitosan particle sizes in Positive Control Paint 2 in the 60-micron range and larger. Example Paint 1 shows particle sizes of 12 to 16 microns and smaller. Notably, the average particle size of Attagel Clay 40 (available from BASF Catalyst LLC), the largest non-chitosan particle in Positive Control Paint 2 or Example Paint 1 is 12 microns (as provided by the manufacturer). The differences in quality of appearance is further evident between the Positive Control Paint 2 and Example Paint 1 in FIGS. 2A and 2B. FIG. 2A shows Positive Control Paint 2 at 80× magnification using a Keyence optical microscope, and FIG. 2B shows Example Paint 1 at 80× magnification using a Keyence optical microscope. Drawdowns of both paints were formed using a 4-mil bird bar on white Leneta charts (available from the Leneta Co.).

(69) Thermocycling Testing

(70) Thermocycling testing was conducted on Positive Control Paint 1 and Example Paint 1 as shown below in Table 2. Cracking was evaluated and rated according to ASTM D661-93 and blistering was evaluated and rated according to ASTM D714-02. Films were applied using 1-inch wide paint brushes (polyester/nylon blend or china bristle) to three types of substrates for each paint. Two coats were applied for each sample with 24 hours dry time at 40° F. and 75% relative humidity for each coat, before heat or cold was applied for testing. Samples were then subjected to freezing or heating in accordance with the test method. The abbreviations in Table 2 correspond to the following substrates: GRA=Glossy red alkyd (alkyd paint applied over redwood 6×18 in. section); CLTX=Chalky latex (latex paint applied over redwood; 6×18 in. section); SYP=Southern yellow pine (uncoated; 6×18 in. section). Samples were made in triplicate and measurements averaged, yielding the below values.

(71) TABLE-US-00002

TABLE 2	Thermocycling	GRA	GRA	CLTX	CLTX	SYP	SYP	Paint	Blister
		Crack	Blister	Crack	Blister	Crack	Blister	Positive	Control
4	10	8	10	10	10	Control	Paint	1	Example
7	10	10	10	10	10	Paint	1	Example	7
10	10	10	10	10	10	Paint	1	Example	10

Elongation Testing

(72) Elongation testing was conducted on Positive Control Paint 1 and Example Paint 1 as shown below in Table 3. Percent elongation was evaluated according to ASTM D2370-16. Films were made using a 10-mil 8-path bar to draw wet paint over standard release paper. This first coat was allowed to dry 1 day at 23° C. and 50% humidity. A second coat was drawn down using the same 8-path bar perpendicular to the first coat and allowed to dry for 7 days at 23° C. and 50% humidity. Films were peeled off of release paper and then cut to half-inch by 3-inch samples. Tensile and elongation testing was conducted on sample films using an Instron Tensiometer. Ten specimens were generated from each paint, with the five highest tensile strength samples selected for each paint and corresponding measurements averaged, yielding the below values (± indicating standard deviation).

(73) TABLE-US-00003

TABLE 3	% Tensile	Paint	Elongation	Strength (psi)	Positive	Control	Paint
1	181.7 ± 18.3	354.9 ± 1.5	Example	Paint 1	249.8 ± 2.1	221.1 ± 1.4	

Resistance to Leaching Testing

(74) To characterize leaching of materials from paint films formed of the comparative and exemplary paints, Algal defacement testing was conducted on Positive Control Paint 1, Negative Control Paint, and Example Paint 1 generally following the method of ASTM D5589-19. Films were made by making drawdowns of each paint on #41 Whatman filter paper using a 4-mil Bird bar. Films were allowed to dry for 24 hours before being cut into 1-inch by 1-inch squares. Samples were immersed in standard deionized water for 48 hours to remove any mobile ions or water-soluble components that might affect the test. Samples were then placed on solidified B-11 agar plates. Samples were inoculated with 350 µL of an algae mixture including *Chlorella vulgaris* var *viridis*, *Oscillatoria lutea*, *Scenedesmus quadricauda*, and *Ulothrix gigas*. Samples were then placed in a Percival incubation chamber at constant temperature (25° C.) with a fluorescent light source to initiate growth. Samples were observed at 3 weeks following inoculation. FIG. 5A shows Positive Control Paint 1 at three weeks from inoculation, FIG. 5B shows Negative Control Paint at

three weeks from inoculation, and FIG. 5C shows Example Paint 1. Ordinarily, ASTM D5589-19 is used for showing resistance to algal defacement, but as will be appreciated by one having skill in the art, observations from samples subjected to this test also show resistance to leaching. This can be observed in the absence of a “zone of inhibition” surrounding the painted filter paper substrate of Example Paint 1 shown in FIG. 5C and the presence of a zone of inhibition for both Positive Control Paint 1 (FIG. 5A) and Negative Control Paint (FIG. 5B).

(75) Susceptibility to Fungal/Mildew Defacement

(76) To illustrate reduced susceptibility to fungal/mildew defacement of the exemplary dried paint films, Positive Control Paint 1 and Experimental Paint 1 were applied to aluminum panels (available from Q-Lab, Westlake, OH) as well as Hardie board substrate. A 10 mil 8-path bar was used to apply each paint to the aluminum panels to give a final coating thickness of approx. 5 mil wet. The paints were applied to Hardie board by brush (2 coats) to give a similar final finish of 5 mil wet. Both sample sets were prepared in triplicate and allowed to cure fully under ambient conditions for 1 week prior to placement in a mildew cabinet with environmental control.

Throughout the experiment, the mildew cabinet was kept at 90° F. (+2° F.) at 95-98% humidity. Vermiculite pieces were inoculated with *Aspergillus niger*, *Penicillium* Sp., and *Aureobasidium pullans* species fungal spores and placed on the mildew cabinet floor. The painted aluminum panels and Hardie board were hung randomly on racks in the mildew cabinet with no panel or board touching another or directly touching the inoculated vermiculite. Measurements are made by rating each panel or board according to the scale provided below in Table 4 and then averaging the triplicate results for each paint after 19 weeks of exposure. FIG. 3A shows a Hardie board painted with Positive Control Paint 1, FIG. 3B a Hardie board painted with Negative Control Paint, FIG. 3C shows a Hardie board painted with Example Paint 1, FIG. 3D shows a Hardie board painted with Example Paint 2, and FIG. 3E shows a Hardie board painted with Example Paint 3. FIG. 3A shows an aluminum panel painted with Positive Control Paint 1, FIG. 3B an aluminum panel painted with Negative Control Paint, FIG. 3C shows an aluminum panel painted with Example Paint 1, FIG. 3D shows an aluminum panel painted with Example Paint 2, and FIG. 3E shows an aluminum panel painted with Example Paint 3. All boards and panels are shown after 19 weeks in a mildew chamber, when the ratings were made.

(77) TABLE-US-00004 TABLE 4 Rating Relative Mildew Growth 0 0% panel covered with growth 3 30% panel covered with growth 5 50% panel covered with growth 7 70% panel covered with growth 10 100% panel covered with growth

(78) Rating results are provided below in Table 5. Reported ratings are the average of triplicate sample runs for each paint on each substrate.

(79) TABLE-US-00005 TABLE 5 Hardie Board Aluminum Paint Substrate Panel Substrate

Positive Control Paint 1 1 1 Negative Control Paint 4 5 Example Paint 1 0 1 Example Paint 2 2 1 Example Paint 3 3 1

Claims

1. A coating composition comprising: (a) a carrier liquid; (b) a binder polymer; and (c) chitosan precipitated from an acidic solution of chitosan; wherein the coating composition has a pH above 7.
2. The coating composition of claim 1, wherein the chitosan is precipitated using ammonia.
3. The coating composition of claim 1, wherein the carrier liquid comprises water.
4. The coating composition of claim 1, wherein the coating composition further comprises pigment.
5. The coating composition of claim 1, wherein the coating composition comprises 13% to 30% by weight pigment and the pigment is titanium dioxide.
6. The coating composition of claim 1, wherein the coating composition has a pigment volume concentration (PVC) below 60.
7. The coating composition of claim 1, wherein the coating composition has about 25% to about

65% by weight solids.

8. The coating composition of claim 7, wherein the coating composition has about 30% to about 60% by weight solids.

9. The coating composition of claim 1, wherein the coating composition comprises about 0.02% to about 1.0% by weight chitosan.

10. The coating composition of claim 1, wherein the precipitated chitosan has a particle size of less than 16 microns in the coating composition.

11. The coating composition of claim 1, wherein a film formed from the dried coating composition has a Hegman gauge rating of 5 or higher.

12. The coating composition of claim 1, wherein the coating has a viscosity under 120 KU.

13. A coated article, coated in the coating composition of claim 1.

14. A method of making a coating composition of claim 1, the method comprising: (a) adding chitosan in an acidic chitosan to a grind during a pigment grind stage; (b) during the pigment grind stage, adding a base to the grind fluid to precipitate the chitosan and applying shear to the grind; (c) blending the grind with carrier liquid and binder polymer to form a coating composition.
