

# US Patent & Trademark Office

## Patent Public Search | Text View

---

|                      |                    |
|----------------------|--------------------|
| United States Patent | 12416554           |
| Kind Code            | B2                 |
| Date of Patent       | September 16, 2025 |
| Inventor(s)          | Brovold; Shawn     |

---

### Material performance testing including improved load detection

---

#### Abstract

A material testing apparatus includes an actuator to apply a force to a load head according to electronic control signals. The load head supplies a load to a material specimen in a first dimension. A plurality of load line displacement (LLD) reference points extend radially outward from the load head; and a plurality of LLD measuring devices correspond to the plurality of LLD reference points. Each LLD measuring device is positioned to detect a position of a corresponding LLD reference point along the first dimension and is configured to transmit position signals to a controller programmed to perform a performance test on the material specimen using feedback control based on a combination of the position signals, including an average of the position signals.

---

|                   |                                                                           |
|-------------------|---------------------------------------------------------------------------|
| <b>Inventors:</b> | <b>Brovold; Shawn (Edina, MN)</b>                                         |
| <b>Applicant:</b> | <b>Troxler Electronic Laboratories, Inc. (Research Triangle Park, NC)</b> |
| <b>Family ID:</b> | <b>1000008820132</b>                                                      |
| <b>Assignee:</b>  | <b>Troxler Electronic Laboratories Inc (N/A, NC)</b>                      |
| <b>Appl. No.:</b> | <b>18/377877</b>                                                          |
| <b>Filed:</b>     | <b>October 09, 2023</b>                                                   |

#### Prior Publication Data

| Document Identifier | Publication Date |
|---------------------|------------------|
| US 20240118180 A1   | Apr. 11, 2024    |

#### Related U.S. Application Data

continuation parent-doc US 17473446 20210913 US 11781957 child-doc US 18377877  
continuation parent-doc US 16865993 20200504 US 11119017 20210914 child-doc US 17473446  
continuation parent-doc US 15864465 20180108 US 10641690 20200505 child-doc US 16865993  
us-provisional-application US 62443628 20170106

---

## Publication Classification

**Int. Cl.:** G01N3/08 (20060101); G01N3/20 (20060101); G01N33/42 (20060101)

**U.S. Cl.:**

**CPC** G01N3/08 (20130101); G01N3/20 (20130101); G01N33/42 (20130101);  
G01N2203/0062 (20130101)

## Field of Classification Search

**USPC:** None

---

## References Cited

### U.S. PATENT DOCUMENTS

| Patent No. | Issued Date | Patentee Name | U.S. Cl. | CPC       |
|------------|-------------|---------------|----------|-----------|
| 5048320    | 12/1990     | Mitsubishi    | 73/12.09 | G01M 7/08 |
| 6389876    | 12/2001     | Tanimura      | 73/12.09 | G01N 3/06 |
| 8825423    | 12/2013     | Brovold       | 702/41   | G01N 3/08 |
| 10641690   | 12/2019     | Brovold       | N/A      | G01N 3/08 |
| 11781957   | 12/2022     | Brovold       | 73/818   | G01N 3/08 |

### OTHER PUBLICATIONS

Standard Method of Test for Determining the Fracture Potential of Asphalt Mixtures Using Semicircular Bend Geometry (SCB) at Intermediate Temperature, American Association of State Highway and Transportation Officials, Aug. 2016, 13 pages. cited by applicant

Determining the Fracture Potential of Asphalt Mixtures Using the Illinois Flexibility Index Test (I-FIT), Illinois Test Procedure 405, Jan. 2016, 12 pages. cited by applicant

Standard Test Method for Determining Fracture Energy of Asphalt-Aggregate Mixtures Using the Disk-Shaped Compact Tension Geometry, ASTM International, Designation: D 7313-07, 2007, 7 pages. cited by applicant

USPTO, Non-Final Office Action for corresponding U.S. Appl. No. 15/864,465 dated Jun. 26, 2019, 13 pages. cited by applicant

USPTO, Non-Final Office Action for corresponding U.S. Appl. No. 16/865,993 dated Feb. 17, 2021, 10 pages. cited by applicant

USPTO, Non-Final Office Action for corresponding U.S. Appl. No. 17/473,446 dated Sep. 26, 2022, 13 pages. cited by applicant

USPTO, Final Office Action for corresponding U.S. Appl. No. 17/473,446 dated Feb. 9, 2023, 15 pages. cited by applicant

---

*Primary Examiner:* Breene; John E

*Assistant Examiner:* Plumb; Nigel H

*Attorney, Agent or Firm:* NK Patent Law PLLC

---

## Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 17/473,446 filed Sep. 13, 2021, being issued as U.S. Pat. No. 11,781,957 on Oct. 10, 2023, which is a continuation of U.S. patent application Ser. No. 16/865,993 filed May 4, 2020, now U.S. Pat. No. 11,119,017 issued Sep. 14, 2021, which is a continuation of U.S. patent application Ser. No. 15/864,465 filed Jan. 8, 2018, now U.S. Pat. No. 10,641,690 issued May 5, 2020, which claims the benefit of U.S. Provisional Ser. No. 62/443,628 filed Jan. 6, 2017. This disclosure of the prior applications is considered part of (and is incorporated by reference in) the disclosure of this application.

### TECHNICAL FIELD

(1) This specification generally relates to systems, techniques, apparatuses, and devices for improved displacement control of loading apparatuses used for performance testing of constructions materials, such as asphalt, concrete, masonry, structural steel, soil, and others.

### BACKGROUND

(2) Testing protocols and control systems have been developed to test the fracture properties of asphalt. For example, Illinois Test Procedure 405 has been developed and published by the Illinois Department of Transportation for determining the fracture potential of asphalt mixtures using the Illinois Flexibility Index Test (I-FIT). As part of this test, an asphalt pavement core or Superpave Gyratory Compactor (SGC) compacted asphalt mixture specimen is trimmed and cut in half to create a semicircular shaped test specimen. A notch is sawn in the flat side of the semicircular specimen opposite the curved edge. The specimen is conditioned and maintained through testing at 25° C. (77° F.). The specimen is positioned in the fixture with the notched side down centered on two rollers. A load is applied along the vertical radius of the specimen and the loads and Load Line Displacement (LLD) are measured during the entire duration of the test. The load is applied such that a constant LLD rate of 50 mm/min is obtained and maintained for the duration of the test.

(3) In a related standard, the American Association of Street Highway and Transportation Officials (AASHTO) AASHTO Designation TP 124-16 also describes the method of testing for determining the fracture potential of asphalt mixtures using semicircular bend geometry (SCB) at intermediate temperatures, similar to the I-FIT test.

### SUMMARY

(4) This document generally describes systems and control techniques for improved displacement control of loading apparatuses used for performance testing of materials, such as for the I-FIT and ASSHTO fracture potential tests. In particular, previous control systems and apparatuses have relied on the use of a singular LLD measurement device that is cantilevered off the side of the load head to provide LLD measurements, which are then used to control the LLD rate being applied to the specimen under test and to determine the ultimate flexibility index (FI) for the specimen. The FI measurement can indicate how well an asphalt specimen under test can carry a load after it has reached an initial structural breaking point. To provide accurate, consistent, and reliable FI measurements, a testing apparatus and control system needs to be able to accurately measure displacement of the load head and to account for deformation of the head during testing to ensure a consistent rate of LLD is applied to the specimen. Measurements being off by as much as 1/1000" can cause the FI measurement to be incorrect by significant amounts—potentially providing false positives for failing specimens.

(5) As described throughout this document, improved displacement control can be achieved in a variety of ways, such as through the use of multiple LLD measurement devices (e.g., multiple displacement transducers, other suitable LLD measurement devices) to provide multiple LLD measurements that can be combined to calculate a more accurate position and/or position rate

(velocity) for the load head. Control of an actuator driving the load head can additionally be improved by using the more accurate position and/or position rate information, which can provide for more consistent and reliable LLD rate during testing, and ultimately more accurate and reliable FI measurements for the sample under test.

(6) Multiple LLD measurements taken at the same time from multiple displacement transducers can be combined in any of a variety of ways, such as through averaging the values, using weighted averages (e.g., weighting based on any of a variety of factors), median values, and/or other combinations of values.

(7) Multiple LLD measurement devices, such as multiple displacement transducers, can be located on opposing or near-opposing sides of a specimen under test so that bending moments in the load head (and/or other variations in the position of the LLD measurement devices not attributable to the deformation of the specimen under test and/or the load head) can be accounted for and discounted. Such positioning variations in a LLD measurement device can introduce errors that can dramatically alter the LLD rate and the ultimate FI measurement for a test if unaccounted for. For example, with a single cantilevered LLD measurement device off of one side of a specimen under test, prior apparatus and control systems (e.g., I-FIT test) may not be able to detect or correct for such positioning variations that are not attributable to the specimen under test or the load head, and may instead be interpreted as part of the LLD measurement for the specimen under test and/or the load head. The disclosed technology improves upon the accuracy of such control systems and apparatuses by accounting and correcting for such variations, which should not be attributed to either the specimen under test or the load head in order to ensure an accurate FI test result. For example, by combining measurements from multiple LLD measurement devices (e.g., using the average of multiple displacement transducers) from particularly selected reference points on a machine, the bias introduced by machine compliance can be cancelled, resulting in a more accurate measurement of displacement and loading rate control of the specimen under test.

(8) In one implementation, a material testing apparatus includes an actuator to drive a piston according to electronic control signals; a load head to supply a load to a material specimen in a first dimension, wherein force is applied to the load head by the piston; a plurality of load line displacement (LLD) reference points that extend radially outward from the load head; a plurality of LLD measuring devices that correspond to the plurality of LLD reference points, each of the plurality of LLD measuring devices (i) being positioned to detect a position of a corresponding LLD reference point along the first dimension and (ii) being configured to transmit position signals to a controller; and a load cell to measure the load supplied to the material specimen by the load head, wherein the load cell is configured to transmit load signals to the controller.

(9) Such material testing apparatus can optionally include one or more of the following features. The plurality of LLD measuring devices can include a plurality of transducers. The plurality of LLD reference points can include a plurality of magnets. The plurality of transducers can include a plurality of non-contact magneto restrictive position transducers that measure the positions of the plurality of magnets along the first dimension. The plurality of magnets can extend radially outward from the load head in a second dimension that is substantially perpendicular to the first dimension. The plurality of magnets can extend from opposing sides of the load head. The plurality of non-contact magneto restrictive position transducers can be positioned on opposing sides of the material specimen. The material specimen can be an asphalt specimen. The controller can be programmed to perform a flexibility index (FI) test on the asphalt specimen using feedback control based on (i) a combination of the position signals from the plurality of non-contact magneto restrictive position transducers and (ii) the load signal from the load cell. The controller can provide the control signals to the actuator according to the feedback control so that a target rate of LLD is achieved during the FI test. The target rate of LLD can be 50 mm/minute. The combination of the position signals can include an average of the position signals. The controller can be separate from the apparatus. The apparatus can further include the controller, wherein the controller is

programmed to perform a performance test on the material specimen using feedback control based on (i) a combination of the position signals from the plurality of LLD measuring devices and (ii) the load signal from the load cell, and wherein the controller determines and provides the control signals to the actuator according to the feedback control so that a target rate of LLD is achieved during the performance test. The combination of position signals can include an average of the position signals.

(10) In another implementation, a material testing system includes an actuator to drive a piston according to electronic control signals; a load head to supply a load to a material specimen in a first dimension, wherein force is applied to the load head by the piston; a plurality of load line displacement (LLD) reference points that extend radially outward from the load head; a plurality of LLD measuring devices that correspond to the plurality of LLD reference points, each of the plurality of LLD measuring devices (i) being positioned to detect a position of a corresponding LLD reference point along the first dimension and (ii) being configured to transmit position signals; a load cell to measure the load supplied to the material specimen by the load head, wherein the load cell is configured to transmit load signals; and a controller configured to (i) perform feedback control of the actuator based, at least in part, on the position signals and the load signals during a performance test of the material specimen, (ii) record data during the performance test, and (iii) determine a result for the performance test based on the recorded data.

(11) Such a material testing system can optionally include one or more of the following features. The feedback control includes repeatedly performing the following during the performance test: receive the position signals from the plurality of LLD measuring devices, receive the load signals from the load cell, combine the position signals into a combined position, determine an LLD measurement for the material specimen based on the combined position, compare the LLD measurement with an target loading rate for the performance test, determine the control signals for the actuator based on the comparison and the load signals, and provide the control signals to the actuator. Combining the position signals can include averaging the position signals and the combined position can be an average position. The performance test can include an FI test. The material specimen can include an asphalt specimen. The data that is recorded can include the average position and the load signals. The result for the FI test can be an FI result value. The target loading rate can include 50 mm/minute. The plurality of LLD measuring devices can include a plurality of transducers. The plurality of LLD reference points can include a plurality of magnets. The plurality of transducers can include a plurality of non-contact magneto restrictive position transducers that measure the positions of the plurality of magnets along the first dimension. The plurality of magnets can extend radially outward from the load head in a second dimension that is substantially perpendicular to the first dimension. The plurality of magnets can extend from opposing sides of the load head. The plurality of non-contact magneto restrictive position transducers can be positioned on opposing sides of the material specimen. The material specimen can include an asphalt specimen. The controller can be programmed to perform a flexibility index (FI) test on the asphalt specimen using feedback control based on (i) a combination of the position signals from the plurality of non-contact magneto restrictive position transducers and (ii) the load signal from the load cell. The controller can provide the control signals to the actuator according to the feedback control so that a target rate of LLD is achieved during the FI test. The target rate of LLD can be 50 mm/minute. The combination of the position signals can include an average of the position signals. The plurality of LLD measuring devices can include two LLD measuring devices. The plurality of LLD measuring devices can include four LLD measuring devices.

(12) In another implementation, a method for performing a performance test on a material specimen includes performing feedback control on a material testing apparatus that includes (i) a load head to supply a load to a material specimen, (ii) a plurality of load line displacement (LLD) reference points that extend radially outward from the load head, (iii) a plurality of LLD measuring devices to provide position signals indicating positions of the plurality of LLD reference points,

and (iv) a load cell to provide load signals for the load supplied to the material specimen, the feedback control including repeatedly performing the following: receiving the position signals from the plurality of LLD measuring devices, receiving the load signals from the load cell, combining the position signals into a combined position, determining an LLD measurement for the material specimen based on the combined position, comparing the LLD measurement with an target loading rate for the performance test, determining the control signals for the actuator based on the comparison and the load signals, and providing the control signals to the actuator; and determining a result for the material specimen under the performance test based on, at least, changes in the combined position and the load signals during the performance test.

(13) Certain implementations can provide one or more of the following advantages. For example, the disclosed technology can improve upon the accuracy, reliability, and consistency of FI tests that are performed on asphalt samples by reducing measurement error. Additional and/or alternative advantages are also possible, as described below.

---

## Description

### BRIEF DESCRIPTION OF THE ATTACHMENTS

(1) FIG. 1 is a conceptual diagram of an example control system for performing improved displacement control of an example loading apparatus for performance testing of a material specimen under test.

(2) FIGS. 2A-B are simplified models of the example apparatus experiencing a bending moment while the specimen is under test.

(3) FIG. 3 is a block diagram of an example feedback control system for a machine the uses a combination of multiple displacement measuring devices to control and measure the displacement rate of an actuator that is used to apply load to a specimen under test.

(4) FIGS. 4A-F are varied views of the example apparatus depicted with multiple transducers to provide improved material test results.

(5) FIGS. 5A-C present varied views of another apparatus with multiple transducer to provide improved material test results.

(6) FIG. 6 is a graph with example FI test results using the example control systems and apparatuses.

(7) FIGS. 7A-C are graphs of example FI test results using the example control systems and apparatuses.

(8) FIG. 8A depicts an example prior art device that measures displacement using stroke as the measure of LLD.

(9) FIG. 8B is a graph comparing test results using stroke measurements to a combined displacement value determined from multiple transducers.

(10) FIGS. 9A-E depict an example comparison of average LLD measurements versus a stroke displacement measurement.

(11) FIG. 10 is a photograph of another material testing apparatus that can use multiple displacement measuring devices for the load head to control testing in a feedback loop and to additionally provide improved testing results.

(12) FIG. 11 is a side view of an example DCT test specimen.

(13) Like reference numbers and designations in the various drawings indicate like elements.

### DETAILED DESCRIPTION

(14) FIG. 1 is a conceptual diagram of an example control system **100** for performing improved displacement control of an example loading apparatus **102** for performance testing a material specimen **116** under test. In the depicted example, the apparatus **102** is performing a test on a SCB specimen **116**, which is a semi-circular shape or half-disk of a material, such as an asphalt mixture.

The apparatus **102** is designed to apply a load via a load head **108** to the specimen **116**, which can be loaded in a three point bend configuration, for example. The load is applied by an actuator **104** (e.g., hydraulic actuator) which can drive the load head **108** along a load column **110** onto the specimen **116**. For example, the top loading head **108** can use a pivoting rounded loading strip to contact the middle of the specimen **116**, and force can be applied using a hydraulic actuator (example of actuator **104**).

(15) The apparatus **102** includes sensors to provide feedback signals to a controller **122** that is controlling application of the actuator **104** to provide, for example, a target LLD rate to the specimen **116** (e.g., driving the load head **108** at a target LLD rate of 50 mm/min). These sensors can include, for example, a load cell **106** to measure the load that is being applied to the specimen **116** and multiple transducers **114a-b** (example LLD measuring devices) to provide measurements of the LLD. The transducers **114a-b** measure the position of LLD reference points that are defined by reference point devices **112a-b** (e.g., magnets) that are cantilevered off either side of the load head **108**. For example, the transducers **112a-b** can be non-contact magneto restrictive position sensors/transducers that measure the position of magnets (example reference point devices **112a-b**) on the left and right side of the loading fixture **108**. In another example, the transducers **112a-b** can be contact-type LVDTs (or other contact-type transducers) that can be physically contacted by physical objects (example reference point devices **112a-b**) and/or can be placed directly on the specimen **116** to measure displacement (instead of or in addition to using reference points **112a-b**). In this example, by averaging multiple contact-type sensors on the specimen **116**, a high level of rate controllability and measurement can be achieved. Other types of position sensors can be used to directly measure on the specimen **116**, such as extensometers (a type of reusable strain gauge). In a further example, other types of sensors (e.g., optical sensors, radiation sensors, vibration sensors, movement sensors, altimeters) can be used as the transducers **112a-b** and corresponding position indicators (e.g., light sources, radiation sources) can be used as the reference point devices **112a-b**, where appropriate.

(16) As the load is being applied to the specimen **116**, the load cell **106** can transmit load signals **132** to the controller **122**, and the transducers **114a-b** can transmit left and right position signals **130a-b** to the controller **122**. The controller **122**, which can be any of a variety of appropriate computing devices (e.g., embedded controller, application-specific integrated circuit (ASIC), laptop/desktop computer, mobile computing device) that are configured to receive the signals **130a-b** and **132**, and to control the apparatus **102**, can receive the signals and use them to determine the left and right positions for the head **108**, and to combine the determined left and right positions (**140**). For example, the head **108** may have a bending moment **160** that may cause the head to pivot to the left or to the right. When this happens, each of the positions by themselves may inaccurately provide the displacement of the loading head **108**. However, by combining the positions, the inaccuracies of each position can be canceled out to provide an accurate displacement for the head **108**. In prior systems that used just a single transducer, such inaccuracies would not be recognized or eliminated from the head **108** displacement determination. The left and right positions can be combined in any of a variety of ways, such as through averaging, weighted averaging, determining the median value, and/or other appropriate techniques for statistically combining values.

(17) Using the combined position information, the controller **112** can determine the displacement (e.g., LLD) for the head **108** and/or the specimen **116** (**142**), and can control the loading rate based on the combined position, the determined displacement, and/or the load measurement from the load cell **106**. The loading rate can be determined so that the LLD rate is consistent and within an acceptable threshold of a target LLD rate (e.g., 50 mm/min). Control signals **150** can be transmitted to the actuator **104** by the controller **122**. The steps **140-142** can be continually and repeatedly performed by the controller **122** to consistently control the loading rate for the sample **116** during the test.

(18) The controller **122** can additionally record the displacement and load values over time during application of the test in order to calculate the results for the specimen **116**. For example, the controller **122** can determine the FI for the specimen **116** by analyzing the displacement and load over time.

(19) FIGS. 2A-B are simplified models of the example apparatus **102** experiencing a bending moment **160** while the specimen **116** is under test.

(20) Referring to FIG. 2A, in the depicted example model the two loading columns and the single load cell are represented by springs. In some cases, a loading base **120** is supported a support shaft (or load cell), which can also be represented by a spring. The spring stiffness of load Col1 and Col2 are indicated by the  $K_{sub.Col1}$  and  $K_{sub.Col2}$ , respectively. The load cell and support shaft stiffness is represented by  $K_{sub.LC}$  and  $K_{sub.SS}$ , respectively. As the specimen is loaded, the loading columns, load cell, and support shaft all deflect by a value proportional to their stiffness. The amount of deflection is represented by the value  $X$  for each component.

(21) In this example, the deformation of the specimen **160** (as indicated by the crack **170**) is estimated by the relative difference between a reference point on the loading head **108** and loading base **120**, referred to here as Load Line Displacement (LLD). When a bending moment **160** is induced on the loading head and loading base, the magnitude of the left side displacement ( $LLD_L$ , **130a**) will not be the same as the displacement of the right side displacement ( $LLD_R$ , **130b**). Accordingly, if only one of the  $LLD_L$  (**130a**) or  $LLD_R$  (**130b**) values were used by the controller **122**, the ultimate FI results determined by the controller **122** would be different and inaccurate. By including devices **114a-b** to measure both  $LLD_L$  and  $LLD_R$ , the controller **122** can account for the differing magnitude on the left and right sides to more accurately and consistently determine the LLD, and to more accurately determine the ultimate FI results for the specimen **116**.

(22) Referring now to FIG. 2B, this model shows the exaggerated compliance of the two loading columns, single load cell, and support shaft (as compared with the model in FIG. 2A). The deflection of the loading columns, load cell, and support shaft is not always uniform or predictable. Since the crack **170** is not uniform, as the specimen **116** breaks, a moment **160** (bending force) is induced on the loading frame components. This means that Col1 can deflect a different amount than Col2, and the loading head **108** and/or loading base **120** can compress and pivot. Using any of these elements as reference points in the estimation of the specimen **116** deformation can be introduce measurement bias. As shown in this example the displacements of  $LLD_L$  (**130a**) and  $LLD_R$  (**130b**) are not equal. Variation can additionally be introduced through different loading frames and fixtures that have different stiffness, and different components that deflect differently under load. Therefore, to reduce variability in the test results, the apparatus **102** can be equipped with multiple transducers **114a-b** and the controller **122** can be programmed to combine multiple position measurements in order to mitigate the effects of frame and fixture compliance. For example, using average displacement control by the controller **122** can provide a cancelling effect of side measurement bias from averaging opposite (in the case of 2 transducers) or multiple (more than 2 transducers) sides of the loading fixture.

(23) FIG. 3 is a block diagram of an example feedback control system **300** for a machine (e.g., apparatus **102**) the uses a combination of multiple displacement measuring devices (e.g., transducers) to control and measure the displacement rate of an actuator that is used to apply load to a specimen under test. The system **300** applies to the control of position and/or position rate (using differentiated position).

(24) The system **300** includes an example control element **302**, such as an embedded digital controller, that runs a real-time operating system. The control element **302** can include, for example, PC hardware (e.g., processor, microprocessor, memory) that is part of the embedded controller and that is responsible for running the control algorithms, data acquisition, and signal outputs in both digital and analog form. For example, the controller **122** is one example of the control element **302**.

(25) The system **300** also includes an actuation element **304** that can create linear motion for a loading head. The actuation element **304** can be, for example, a hydraulic actuator, such as the actuator **104**. Movement of a hydraulic actuator can be fed, for example, by a hydraulic pump through a hydraulic servo-valve (a flow control device). Other implementations of the actuation element **304** are also possible, such as mechanical screw drives and/or other load driving devices.

(26) The actuation element **304** drives a loading element **306**, which can include a loading frame and specialized fixtures for each specific test. For example, the loading element **306** can include a loading head (e.g., loading head **108**) attached to the end of the piston rod (through a load cell). The hydraulic cylinder can be held in place through load columns (e.g., 2 columns, 4 columns) attached to a top cross-member and bottom base plate. The base of the loading fixture can include additional points of contact with the specimen under test (e.g., specimen **116**). Other configurations of the loading element **306** are also possible.

(27) The loading element **306**, however, can be susceptible to disturbances, which are errors resulting from machine compliance that includes, but not limited to, stretching of the loading columns, compression of the load cell, compression of the hydraulic piston seals, bending of the fixture caused by non-uniform breaking of the specimen under test, and/or combinations thereof. Each element of the loading fixture can be thought of as a spring with different stiffness. In fact, a load cell can be, by definition, a spring device. Since each machine can have a different stiffness, each machine can have a different magnitude of measurement and control error. The systems **100** and **300** can eliminate the uncertainty caused by such disturbances through control and measurement techniques that leverage multiple position measurements to cancel the effects of errors by combining (e.g., averaging) the multiple measurements to mitigate the effect of such disturbances.

(28) The loading element **306** can apply the load to a specimen under test **308**, which can be an asphalt sample, which is a viscoelastic material. Viscoelastic materials have a unique property in which the stiffness of the material is a function of the displacement rate.

(29) Position measurements can be determined for the system **300** by multiple transducers **310a-n**, which can include any number of transducers measuring position at independent locations relative the specimen under test **308** (e.g., measuring on opposing sides of the specimen **308**). The transducers **310a-n** can measure the position of elements (e.g., reference point magnets) that extend from the loading element **306** (e.g., extend perpendicular to the direction of linear displacement). The position elements can be configured so that they provide readily comparable position measurement values, such as through extending the same or similar distance from a common point (e.g., center point) on the loading element **306**. The transducers **310a-n** can be, for example, non-contact type, magneto restrictive position sensor, such as BALLUFF, model BTL001W. Other possible transducers **310a-n** can include any form of linear variable differential transformer (LVDT). Types of LVDTs can include contact type and/or non-contact type transducers. In another example, a rotary variable differential transformer (RVDT)/motor encoder typically used on a mechanical screw type actuator could additionally and/or alternatively be used.

(30) The position measurements from the transducers **310a-n** can be provided to a combining element **312**, which can be, for example, a routine on a controller (e.g., software on embedded controller) that combines the signals (e.g., averages the signals) and maps the combined position to its own unique feedback channel that is used by the control element **302**. The feedback control loop including the control element **302**, the actuation element **304**, the loading element **306**, the transducers **310a-n**, and the combining element **312** can be used to continually control the loading rate applied to the specimen **308** so that a target rate is achieved, and to record displacement and loading measurements to determine an ultimate test result for the specimen **308** (e.g., FI test result).

(31) FIGS. 4A-F are varied views of the example apparatus **102** depicted in FIG. 1 with multiple transducers **114a-b** to provide improved material test results. FIG. 1 presents a front view of the apparatus **102**. FIGS. 4A-B present angled views of the apparatus **102**. FIGS. 4C-D present varied

perspective views of the apparatus **102**. FIG. **4E** presents a top view of the apparatus **102**. FIG. **4F** presents a perspective view of the apparatus **102** without the specimen **116**.

(32) FIGS. **5A-C** present varied views of another apparatus **500** with multiple transducer **502a-b** to provide improved material test results. In the depicted examples, the apparatus **500** is configured to perform tests on circular material samples, such as asphalt. The apparatus **500** can be used in combination with a controller to perform improved material testing, as described above with regard to FIGS. **1-4**. FIG. **5A** presents a perspective view of the apparatus **500**. FIG. **5B** presents a front view of the apparatus **500**. FIG. **5C** presents another perspective view of the apparatus **500**. As described below with regard to FIG. **10**, the apparatus **500** can be used to perform indirect tension testing (IDT).

(33) FIG. **6** is a graph with example FI test results using the example control systems and apparatuses described above with regard to FIGS. **1-5**. This example shows variability between transducer **1** and transducer **2**. In this case, transducer **1** was mounted on the “left” side of the machine and transducer **2** was mounted on the “right” side of the machine. The average displacement (example combined displacement) is a better representation of the actual displacement of the specimen through the specimen centerline.

(34) By using the average displacement to control the test, more accurate and better control of the specimen displacement rate can be achieved. For example, the desired target displacement rate can be 50 mm/min. In this example, the displacement rate for transducer **1** was 49.54 mm/min and the displacement rate for transducer **2** was 59.54 mm/min. However, using the average displacement to control actuation of the load, a better and more accurate rate of 50.04 mm/min was achieved—much closer to the target rate of 50 mm/min. Since the example FI test depicted uses displacement rate as a means to simulate temperature (using the concept of time-temperature superposition for viscoelastic materials), accurate and consistent rate control is as equally important as temperature control to providing reliable and consistent test results. Variability in rate (as well as temperature) can lead to variability in test results.

(35) FIGS. **7A-C** are graphs of example FI test results using the example control systems and apparatuses described above with regard to FIGS. **1-5**. FIG. **7A** depicts the results if only the left transducer (e.g., transducer **114a**) were to be used to perform the test. FIG. **7B** depicts the results if only the right transducer (e.g., transducer **114b**) were to be used to perform the test. FIG. **7C** depicts the results using a combination of both the left and right transducers (e.g., transducers **114a-b**) to perform the test. Since shape of the plot is used in calculating test results, variability between left and right measurements leads to variable in calculated results. Using the previous example, a flexibility index (FI) is calculated for the left, right, and average values. Here each side (FIGS. **7A-B**) has an 18% difference in flexibility index from the average (FIG. **7C**).

(36) FIG. **8A** depicts an example prior art device that measures displacement using stroke as the measure of LLD. One might ask, if measuring off a cantilevered point induces error, then why don't we measure off of the centerline of the actuator? The position of the actuator piston is often referred to as the “Stroke” measurement. Generally, the reference point of the actuator is a large distance away from the specimen. Since the deflection of any spring is a function of its length, the longer the distance from the specimen, the more deflection that is unaccounted for in the estimate of specimen deflection. Additionally, measuring the position the actuator does not take into account the deflection of the loading columns, load cell and support shaft. From example device depicted in FIG. **8A**, as the piston compresses the specimen, the load columns will stretch, and the load cell and support column will compress. This leads to error in the specimen deformation measurement, as well as error in the control of the loading velocity.

(37) Cost can be another issue with centerline actuator displacement measurements. Internal LVDTs, such as the one represented in FIG. **8A**, inside a hydraulic actuator can be very expensive—much more expensive than the transducers and other position measuring devices described above with regard to FIGS. **1-7**.

(38) FIG. 8B is a graph comparing test results using stroke measurements, as described in FIG. 8A, to a combined displacement value determined from multiple transducers, as described in FIGS. 1-7 above. This example shows that, in some cases, there is very little variability between transducer 1 (LLD\_L) and transducer 2 (LLD\_R). In this case, transducer 1 was mounted on the “left” side of the machine and transducer 2 was mounted on the “right” side of the machine. This test also shows how there is typically more deflection measured at the actuator piston; measurement of the actuator piston is referred to as its “stroke.” This is why the Load Line Displacement (LLD) measurement is more accurate for specimen testing than the Stroke measurement, even though stroke is along the centerline of the fixture.

(39) FIGS. 9A-E depict an example comparison of average LLD measurements versus a stroke displacement measurement. FIGS. 9A-C depict FI measurements for a left transducer (FIG. 9A), a right transducer (FIG. 9B), and an average of the two (FIG. 9C).

(40) Using the previous example, in some cases there may not a significant difference between results calculated from a Left and Right transducer. In this case, the left and right flexibility index (FI) was within 1% of the average. Since the amount of bias is not always predictable, it is not reliable to assume that test results are unbiased; the only certain way to determine the bias is to measure it. The way to remove the bias is to cancel it out by combining the values, such as through averaging them.

(41) FIGS. 9D-E provide a comparison of the average LLD determination (FIG. 9D) and measurements from an actuator stroke (FIG. 9E). The measurement of actuator stroke is not as reliable as Load Line Displacement (LLD). In the previous example, despite the fact that the results from the left and right LLD measurements were consistent with the average, the measurement of stroke was not consistent. The additional deflection picked up in the stroke measurement resulted in a 14% reduction in flexibility index (FI). Since a higher flexibility index value is desirable, measuring stroke falsely degrades the calculated results.

(42) FIG. 10 is a photograph of another material testing apparatus that can use multiple displacement measuring devices for the load head to control testing in a feedback loop and to additionally provide improved testing results. In the depicted example, an indirect tension (IDT) testing machine is depicted, which is somewhat different from the SCB machines described above. In particular, with the IDT machine the specimen is a full disk instead of a half-disk like on the SCB machine. The frame consists of four posts for increased stiffness due to higher load capacity. The load cell is mounted to the base plate instead of the actuator rod. A single top and bottom loading strip of equal design are used to contact the specimen. The displacement transducers are mounted to the load cell, and the reference magnets are mounted to the sides of the loading head. Examples of an IDT machine are depicted above with regard to FIGS. 5A-C.

(43) The features described above can be applied to other testing machines and control systems. For example, in addition to averaging values on two opposing sides of the loading fixture, a testing apparatus could include three, four, five, six, and/or other numbers of transducers providing values that are combined (e.g., averaged). If the bias in a loading frame and/or specimen is complex enough, additional transducers and reference locations may provide improved controllability and estimation of the deformation of the specimen under test. With three or more transducers, the bending movement can be resolved along more than one axis relative to the specimen. The techniques, systems, apparatuses, and devices described in this document can additionally be applied to performance tests that load the specimen in tension, and/or measure the deformation of the specimen through the use of displacement transducers and/or reference points mounted directly on the specimen. For example, the Disk-shaped Compact Tension (DCT) test (e.g., described by the ASTM D7313 standard) applies a tensile load to the specimen and uses a single clip-on displacement (COD) gauge mounted on the specimen to control and measure the rate of displacement at the specimen's crack mouth. The features described above can be applied to a DCT test in a variety of ways, such as through the inclusion and use of multiple displacement measuring

devices (e.g., multiple displacement gauges). For example, a DCT test can be modified to include two displacement gauges that are mounted closer to the crack tip on both (left and right) sides of the specimen (see FIG. 11 for example side view of a DCT test specimen). Any non-uniform loading resulting from the interaction between the specimen and the tensile load fixtures, can lead to variability between the measurement on either side of the specimen. For improved controllability and measurement, the techniques described above can be applied to combine the measurements from these multiple displacement gauges to generate a more accurate combined measurement. Other variations and applications of the disclosed techniques, systems, apparatuses, and devices can be applied to DCT tests, other tensile load tests, and/or other compression tests. While this specification contains many specific implementation details, these should not be construed as limitations on the scope of any inventions or of what may be claimed, but rather as descriptions of features specific to particular implementations of particular inventions. Certain features that are described in this specification in the context of separate implementations can also be implemented in combination in a single implementation. Conversely, various features that are described in the context of a single implementation can also be implemented in multiple implementations separately or in any suitable sub-combination. Moreover, although features may be described above as acting in certain combinations and even initially claimed as such, one or more features from a claimed combination can in some cases be excised from the combination, and the claimed combination may be directed to a sub-combination or variation of a sub-combination.

(44) Similarly, while operations are depicted in the drawings in a particular order, this should not be understood as requiring that such operations be performed in the particular order shown or in sequential order, or that all illustrated operations be performed, to achieve desirable results. In certain circumstances, multitasking and parallel processing may be advantageous. Moreover, the separation of various system components in the implementations described above should not be understood as requiring such separation in all implementations, and it should be understood that the described program components and systems can generally be integrated together in a single software product or packaged into multiple software products.

(45) Thus, particular implementations of the subject matter have been described. Other implementations are within the scope of the following claims. In some cases, the actions recited in the claims can be performed in a different order and still achieve desirable results. In addition, the processes depicted in the accompanying figures do not necessarily require the particular order shown, or sequential order, to achieve desirable results. In certain implementations, multitasking and parallel processing may be advantageous.

## Claims

1. A material testing apparatus, the apparatus comprising: an actuator to apply a force; a load head to supply a load to a material specimen, wherein the load head has a moment causing the load head to pivot; two or more load line displacement (LLD) reference points that extend outward from the load head; and two or more measuring devices that correspond to the plurality of LLD reference points, each positioned to detect a position of the corresponding LLD reference points, and to transmit two or more position signals to a controller, wherein the two or more measuring devices are located on opposing or near-opposing sides of the material specimen; and wherein the controller is programmed to perform a performance test on the material specimen that includes detecting a variation in the position of the two or more measuring devices.
2. The material testing apparatus of claim 1, wherein the measuring devices comprise a plurality of transducers.
3. The material testing apparatus of claim 2, further comprising a plurality of magnets along a first dimension.
4. The material testing apparatus of claim 3, wherein the plurality of magnets extend at least

partially radially outward from the load head.

5. The material testing apparatus of claim 3, wherein magneto restrictive position transducers are positioned on opposing sides of the material specimen.

6. The material testing apparatus of claim 3, wherein the material specimen comprises a solid specimen.

7. The material testing apparatus of claim 1, wherein the controller is programmed to perform a flexibility test on the asphalt specimen using feedback control.

8. The material testing apparatus of claim 7, wherein the target rate of LLD is measured in mm/minute.

9. The material testing apparatus of claim 7, wherein the position signals comprise an average.

10. The material testing apparatus of claim 1, wherein the controller is separate from the apparatus.

11. The material testing apparatus of claim 1, wherein the controller performs a flexibility index test.

12. The material testing apparatus of claim 1, wherein the controller provides the control signals so that a target rate of LLD is achieved.

13. A material testing system, the system comprising: an actuator to apply a force; a load head to supply a load to a material specimen, wherein the load head has a moment causing the load head to pivot; two or more load line displacement (LLD) reference points that extend outward from the load head; two or more measuring devices corresponding to the two or more LLD reference points, wherein the two or more measuring devices are located on opposing or near-opposing sides of the material specimen; a load cell to: measure the load supplied to the material specimen; generate a load signal based on the measured load; measure two or more positions of the load head by detecting two or more displacements, caused by the supplied load, of at least a portion of the material specimen and detecting a difference between the two or more displacements; and generate two or more position signals based on the measured load; and a controller configured to receive two or more position signals and the load signal from the load cell, combine the position signals, determine a measurement for the material specimen, and compare the measurement with a target for a performance test.

14. The material testing system of claim 13, wherein the material specimen comprises a solid.

15. The material testing system of claim 14, wherein the target loading rate is measured in mm/minute.

16. A method of performing a performance test on a material specimen, the method comprising: supplying a load to a material specimen using a load head, wherein the load head has a moment causing the load head to pivot; measuring the load supplied to the material specimen; generating a load signal based on the measured load; detecting two or more displacements, caused by the supplied load, of at least a portion of the material specimen; detecting a difference between the two or more displacements that includes using two or more load line displacement (LLD) reference points that extend outward from the load head and two or more measuring devices corresponding to the two or more LLD reference points, wherein the two or more measuring devices are located on opposing or near-opposing sides of the material specimen; and generating two or more position signals based on the two or more detected displacements; determining a characteristic of the material specimen using a combination of the two or more position signals and the load signal.

17. The method of claim 16, wherein detecting a displacement comprises using a displacement transducer positioned along a side of the material specimen.

18. The method of claim 16, further comprising positioning a flat side of the material specimen on two rollers before supplying a load to the material specimen.

19. The method of claim 18, wherein applying the load to a material specimen comprises applying the load to a curved edge of the material specimen opposite the flat side.

20. The method of claim 18, wherein positioning the flat side of the material specimen on two the rollers comprises centering a notch in the flat side relative to the two rollers.

