

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280556

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

LU; Chao-Chun et al.

METHOD FOR FORMING MOS TRANSISTOR STRUCTURE

Abstract

A method for forming a metal-oxide-semiconductor (MOS) transistor structure includes steps as follows: A plurality of fin structures is defined in a semiconductor substrate. A sacrificial spacer is formed surrounding sidewalls of each of the plurality of fin structures. A dielectric layer is formed to surround the sacrificial spacer. And after the sacrificial spacer is removed gate structures are respectively formed covering the sidewalls of each of the plurality of fin structures.

Inventors: LU; Chao-Chun (Hsinchu, TW), HUANG; Li-Ping (Hsinchu, TW)

Applicant: Invention and Collaboration Laboratory, Inc. (Taipei City, TW)

Family ID: 96860876

Assignee: Invention and Collaboration Laboratory, Inc. (Taipei City, TW)

Appl. No.: 18/966937

Filed: December 03, 2024

Related U.S. Application Data

us-provisional-application US 63559956 20240301

us-provisional-application US 63683712 20240816

Publication Classification

Int. Cl.: H10D30/01 (20250101); H01L21/762 (20060101); H10D30/62 (20250101)

U.S. Cl.:

CPC H10D30/024 (20250101); H01L21/76224 (20130101); H10D30/6215 (20250101);

Background/Summary

[0001] This application claims the benefit of U.S. provisional application Ser. No. 63/559,956 filed Mar. 1, 2024, and U.S. provisional Ser. No. 63/683,712, filed Aug. 16, 2024, and the subject matter of which is incorporated herein by reference.

BACKGROUND OF THE DISCLOSURE

Field of the Disclosure

[0002] The present invention relates to a method for forming an integrated circuit, and particularly to a method for forming a metal-oxide-semiconductor (MOS) transistor structure.

Description of the Related Art

[0003] Monolithic integration of Silicon devices for integrated circuits (IC) has achieved realization of more than 50 billions of transistors on a die in the year of 2021, which has been named as an era of GSI (Gigabyte-Scale Integration, i.e. Achieving more than billions of transistors on a die) from VLSI (Very Large Scale Integration having more than millions of transistors on a die). Such accomplishments of making much higher integration capacity of transistors on a die have sharply enabled more powerful Microsystems with significantly improved PPAC (higher Performance, better Power Managing capability, effective usage of Area and lower Cost per bit), thus creating many powerful chips such as CPU, GPU, FPGA, SOC, SRAM, DRAM, etc., which enhances System capabilities so as to continually support Moore's Law which formed a base to create an exponential Economic growth.

[0004] With such a high productivity generated from GSI to grow new applications which stimulates fast growth of economic scale, there are very strong demands to integrate more transistors on a die. So it is expected that Semiconductor industry try every best effort to march toward a Tera-Scale Integration (TSI), that is, Integration of more than trillions of transistors on a die for a chip. Therefore, how to sharply improve the transistor to meet this TSI challenge requires Inventions and engineering improvements of for some fundamentally changed transistor structure with better PPAC. For example, if a chip does integrate one trillion transistors on a die, if each transistor is set at achieving a standby current (or called loff) about 0.5 pA (A is abbreviation of Ampere), then a total of one trillion of transistors will have its loff of a die is approaching 0.5 Amperes.

[0005] The state-of-art transistor with less than 20 nm technologies can hardly achieved this loff of 0.5 pA, however; even by using various transistor structures such as FinFET or Tri-Gate Designs, some loff can be as large as 5 to 10 pA. How to continuously shrink the device dimensions plus to reduce loff (such as lower than 1 pA) is the key challenge.

[0006] An example of state-of-the-art Field-Effect Transistor (FinFET) usually includes an active region which is formed as a Fin structure (as shown in FIG. 1). The transistor gate structure 5 using some conductive material (like metal, polysilicon or polycide, etc.) over an insulator or dielectric layer (such as oxide, oxide/nitride or some high-k dielectric, etc.) is formed over a fin-structure or a 3D silicon surface whose sidewalls are isolated from those of other transistors by using insulation materials (e.g. oxide or oxide/nitride or other dielectrics). Using an NMOS transistor as example, there are source region 11 and drain region 12 which are formed by an ion-implantation plus thermal annealing technique to implant high concentration n-type dopants into a p-type substrate (or a p-well) which thus results in two separated n+/p junction areas. Furthermore, to lessen impact ionization and hot carrier injection prior to highly doped n+/p junction, it is common to form a lightly doped-drain (LDD) region 13 before the highly doped n+ source/drain region 11/12 by Ion-implantation plus thermal annealing technique, and such ion-implantation plus thermal annealing technique frequently causes the LDD regions 13 penetrating into the portion of the 3D active regions which are underneath the gate structure 5. Therefore, the effective channel between the

LDD regions 13 is unavoidably shortened.

[0007] On the other hand, the advancement of manufacturing process technologies is continuing to move forward rapidly by scaling down the geometries of devices in both horizontal and vertical dimensions (such as the minimum feature size called as Lamda (λ) is shrunk from 28 nm down to 5 nm or 3 nm). But many problems are introduced or getting worse due to such FinFET or Trigate geometry scaling.

[0008] For example, as the device gate length is scaled down, the distance of the adjacent two fin structures cannot be well controlled by the conventional lithography and etch patterning technology. Furthermore, the gate electrode pitch or distance of two adjacent MOS transistors can be also hardly controlled as well by the conventional lithography and etch patterning technology.

[0009] In addition, as the device dimension is scaled down to 7 nm, 5 nm or 3 nm, the height of the Fin structure (such as 50-100 nm) is far larger than the width of the Fin structure (such as 3-10 nm) such that the fin structure is vulnerable or even collapsed during the subsequent processes (such as source/drain formation, gate formation, etc.).

SUMMARY OF THE DISCLOSURE

[0010] One object of the present disclosure is to provide a method for forming a metal-oxide-semiconductor (MOS) transistor structure includes steps as follows: Firstly, a first fin structure and a second fin structure adjacent to the first fin structure are defined in a semiconductor substrate, wherein a shallow trench isolation (STI) region is between the first fin structure and the second fin structure. Next, a first sacrificial spacer is formed disposed along sidewalls of the first fin structure; and a second sacrificial spacer is formed disposed along sidewalls of the second fin structure, wherein a gap is between the first sacrificial spacer and the second sacrificial space. Then, an inserting dielectric layer is formed to fill the gap between the first sacrificial spacer and the second sacrificial spacer. After removing the first sacrificial spacer and the second sacrificial spacer, two gate structures are formed over the first fin structure and the second fin structure respectively, wherein the two gate structures are separated by the inserting dielectric layer.

[0011] According to one embodiment of the present disclosure, the first sacrificial spacer and the second sacrificial spacer comprise an epitaxial semiconductor material selectively grown based on the sidewalls of the first fin structure and the second fin structure.

[0012] According to one embodiment of the present disclosure, prior to forming the first sacrificial spacer and the second sacrificial spacer, the method further includes steps as follows: firstly, a capping dielectric layer is formed covering the first fin structure and the second fin structure. And a gate opening is then defined in the capping dielectric layer to make the sidewalls of the first fin structure and the second fin structure partially exposed from the gate opening.

[0013] According to one embodiment of the present disclosure, the method further includes steps of forming a fin spacer to surround the sidewalls of the first fin structure and the second fin structure, prior to forming the capping dielectric layer; and performing at least one etching process to remove the fin spacer in the gate opening to make the sidewalls of the first fin structure and the second fin structure partially exposed, prior to forming the first sacrificial spacer and the second sacrificial spacer.

[0014] According to one embodiment of the present disclosure, the material constituting the inserting dielectric layer is different from that constituting the capping dielectric layer.

[0015] According to one embodiment of the present disclosure, the method further includes steps of deepening the gate opening to expose the semiconductor substrate, after the epitaxial semiconductor material is formed and prior to the gate opening is filled with the inserting dielectric layer.

[0016] According to one embodiment of the present disclosure, a portion of the semiconductor substrate is removed during the process of deepening the gate opening.

[0017] According to one embodiment of the present disclosure, a portion of the STI region is removed during deepening the gate opening, so as to remain another portion of the STI region

beneath the epitaxial semiconductor material.

[0018] According to one embodiment of the present disclosure a bottom of the inserting dielectric layer is lower than a bottom of the another portion of the STI region.

[0019] According to one embodiment of the present disclosure, a dielectric constant of the inserting dielectric layer is lower than that of SiO₂.

[0020] According to one embodiment of the present disclosure, the first sacrificial spacer and the second sacrificial spacer comprises amorphous silicon covering the sidewalls of the first fin structure the second fin structure.

[0021] According to one embodiment of the present disclosure, the method further includes steps of forming a fin spacer to surround the sidewalls of the first fin structure and the second fin structure, prior to forming the first sacrificial spacer and the second sacrificial spacer.

[0022] According to one embodiment of the present disclosure, the method further includes steps of forming a capping dielectric layer covering the first fin structure, the second fin structure, the first sacrificial spacer, the second sacrificial spacer and the inserting dielectric layer; and defining a gate opening in the capping dielectric layer to make the sidewalls of the first fin structure and the second fin structure partially exposed from the gate opening.

[0023] According to one embodiment of the present disclosure, the method further includes steps of removing a portion of the STI region not covered by the first sacrificial spacer and the second sacrificial spacer to expose a portion of the semiconductor substrate, prior to removing the sacrificial spacer.

[0024] According to one embodiment of the present disclosure, a bottom of the inserting dielectric layer is lower than a bottom of another portion of the STI region beneath the first sacrificial spacer and the second sacrificial spacer.

[0025] Another object of the present disclosure is to provide a MOS transistor structure, wherein the MOS transistor structure includes a first active region, a second active region adjacent to the first active region, an inserting dielectric layer, a first trench, a second trench, a first gate structure and a second gate structure. The first active region and the second active region are formed in a semiconductor substrate, wherein a STI region is between the first active region and the second active region. The inserting dielectric layer is disposed between the first active region and the second active region. The first trench is surrounding or over the first active region, wherein the first trench is adjacent to one side of the inserting dielectric layer. The second trench is surrounding or over the second active region, wherein the second trench is adjacent to another side of the inserting dielectric layer. The first gate structure is over the first active region and within the first trench, wherein the first gate structure covers a first portion of the STI region. The second gate structure is over the second active region and within the first trench. Wherein the second gate structure covers a second portion of the STI region; and a distance between the first gate structure and the second gate structure is decided by the inserting dielectric layer.

[0026] According to one embodiment of the present disclosure, the MOS transistor structure further includes a first source region and a first drain region electrically contacting to a first channel within the first active region; and a second source region and a second drain region electrically contacting to a second channel within the second active region. Moreover, a width of the inserting dielectric layer between the first active region and the second active region is not defined by a photolithographic process.

[0027] Yet another object of the present disclosure is to provide a MOS transistor structure, wherein the MOS transistor structure includes a first fin structure, a second fin structure adjacent to the first fin structure; an inserting dielectric layer, an inserting dielectric layer, a first trench, a second trench, a first gate structure and a second gate structure. The first fin structure and the second fin structure are formed in a semiconductor substrate, wherein a STI region is between the first fin structure and the second fin structure. The inserting dielectric layer is disposed between the first fin structure and the second fin structure. The first trench is surrounding or over the first fin

structure, wherein the first trench is adjacent to one side of the inserting dielectric layer. The second trench is surrounding or over the second fin structure, wherein the second trench is adjacent to another side of the inserting dielectric layer. The first gate structure is over the first fin structure and within the first trench, wherein the first gate structure covers a first portion of the STI region. The second gate structure is over the second fin structure and within the first trench. Wherein the second gate structure covers a second portion of the STI region; and a bottom of the inserting dielectric layer is lower than that of the first portion of the STI region or the second portion of the STI region.

[0028] According to one embodiment of the present disclosure, the MOS transistor structure further includes a first source region and a first drain region electrically contacting to a first channel within the first fin structure; and a second source region and a second drain region electrically contacting to a second channel within the second fin structure.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0029] The above and other aspects of the disclosure will become better understood with regard to the following detailed description of the preferred but non-limiting embodiment(s). The following description is made with reference to the accompanying drawings:

[0030] FIG. 1 is a diagram illustrating a FinFET according to the prior art;

[0031] FIG. 2A(1) is a top view illustrating the structure after the fin structures are defined in the semiconductor substrate;

[0032] FIG. 2A(2) is a cross-sectional view taken along the cutting line C2A1 as depicted in FIG. 2A(1);

[0033] FIG. 2A(3) is a cross-sectional view taken along the cutting line C2A2 as depicted in FIG. 2A(1);

[0034] FIG. 2B(1) is a top view illustrating the structure after the capping dielectric layer is formed to cover the fin structures;

[0035] FIG. 2B(2) is a cross-sectional view taken along the cutting line C2B1 as depicted in FIG. 2B(1);

[0036] FIG. 2B(3) is a cross-sectional view taken along the cutting line C2B2 as depicted in FIG. 2B(1);

[0037] FIG. 2C(1) is a top view illustrating the structure after the fin structures are partially exposed from the gate opening;

[0038] FIG. 2C(2) is a cross-sectional view taken along the cutting line C2C1 as depicted in FIG. 2C(1);

[0039] FIG. 2C(3) is a cross-sectional view taken along the cutting line C2B2 as depicted in FIG. 2C(1);

[0040] FIG. 2D(1) is a top view illustrating the structure after the epitaxial semiconductor material is formed;

[0041] FIG. 2D(2) is a cross-sectional view taken along the cutting line C2D1 as depicted in FIG. 2D(1);

[0042] FIG. 2E(1) is a top view illustrating the structure after the gate opening is filled by a dielectric layer;

[0043] FIG. 2E(2) is a cross-sectional view taken along the cutting line C2E1 as depicted in FIG. 2E(1);

[0044] FIG. 2F(1) is a top view illustrating the structure after the gate structures are formed;

[0045] FIG. 2F(2) is a cross-sectional view taken along the cutting line C2F1 as depicted in FIG. 2F(1);

[0046] FIG. 2F(3) is a cross-sectional view taken along the cutting line C2F2 as depicted in FIG. 2F(1);

[0047] FIG. 2G is a perspective view illustrating a semiconductor device with two adjacent MOS transistors formed by the method as shown in FIGS. 2A(1) to 2F(3);

[0048] FIG. 3A(1) is a top view illustrating the structure after the fin structures are defined in the semiconductor substrate;

[0049] FIG. 3A(2) is a cross-sectional view taken along the cutting line C3A1 as depicted in FIG. 3A(1);

[0050] FIG. 3A(3) is a cross-sectional view taken along the cutting line C3A2 as depicted in FIG. 3A(1);

[0051] FIG. 3B(1) is a top view illustrating the structure after the dielectric layer and the capping dielectric layer are formed;

[0052] FIG. 3B(2) is a cross-sectional view taken along the cutting line C3B1 as depicted in FIG. 3B(1);

[0053] FIG. 3B(3) is a cross-sectional view taken along the cutting line C2B2 as depicted in FIG. 3B(1);

[0054] FIG. 3C(1) is a top view illustrating the structure after the fin structures are partially exposed from the gate opening;

[0055] FIG. 3C(2) is a cross-sectional view taken along the cutting line C3C1 as depicted in FIG. 3C(1);

[0056] FIG. 3C(3) is a cross-sectional view taken along the cutting line C3C2 as depicted in FIG. 3C(1);

[0057] FIG. 3D(1) is a top view illustrating the structure after the gate structures are formed;

[0058] FIG. 3D(2) is a cross-sectional view taken along the cutting line C3E1 as depicted in FIG. 3D(1);

[0059] FIG. 3D(3) is a cross-sectional view taken along the cutting line C3D2 as depicted in FIG. 3D(1);

[0060] FIG. 4A(1) is a top view illustrating the structure after the fin structures are defined in the semiconductor substrate;

[0061] FIG. 4A(2) is a cross-sectional view taken along the cutting line C4A1 as depicted in FIG. 4A(1);

[0062] FIG. 4A(3) is a cross-sectional view taken along the cutting line C4A2 as depicted in FIG. 4A(1);

[0063] FIG. 4B(1) is a top view illustrating the structure after the capping dielectric layer is formed to cover the fin structures;

[0064] FIG. 4B(2) is a cross-sectional view taken along the cutting line C4B1 as depicted in FIG. 4B(1);

[0065] FIG. 4B(3) is a cross-sectional view taken along the cutting line C2B2 as depicted in FIG. 4B(1);

[0066] FIG. 4C(1) is a top view illustrating the structure after the fin structures are partially exposed from the gate opening;

[0067] FIG. 4C(2) is a cross-sectional view taken along the cutting line C4C1 as depicted in FIG. 4C(1);

[0068] FIG. 4C(3) is a cross-sectional view taken along the cutting line C4B2 as depicted in FIG. 4C(1);

[0069] FIG. 4D(1) is a top view illustrating the structure after the epitaxial semiconductor material is formed;

[0070] FIG. 4D(2) is a cross-sectional view taken along the cutting line C4D1 as depicted in FIG. 4D(1);

[0071] FIG. 4E(1) is a top view illustrating the structure after the gate openings are deepened to

expose the semiconductor substrate;

[0072] FIG. 4E(2) is a cross-sectional view taken along the cutting line C4E1 as depicted in FIG. 4E(1);

[0073] FIG. 4F(1) is a top view illustrating the structure after the gate opening is filled by a dielectric layer;

[0074] FIG. 4F(2) is a cross-sectional view taken along the cutting line C4F1 as depicted in FIG. 4F(1);

[0075] FIG. 4G(1) is a top view illustrating the structure after the gate structures are formed;

[0076] FIG. 4G(2) is a cross-sectional view taken along the cutting line C4G1 as depicted in FIG. 4G(1);

[0077] FIG. 4G(3) is a cross-sectional view taken along the cutting line C4G2 as depicted in FIG. 4G(1);

[0078] FIG. 5A(1) is a top view illustrating the structure after the fin structures are defined in the semiconductor substrate;

[0079] FIG. 5A(2) is a cross-sectional view taken along the cutting line C5A1 as depicted in FIG. 5A(1);

[0080] FIG. 5A(3) is a cross-sectional view taken along the cutting line C5A2 as depicted in FIG. 5A(1);

[0081] FIG. 5B(1) is a top view illustrating the structure after the portion of the STIs not covered by the fin spacers is removed;

[0082] FIG. 5B(2) is a cross-sectional view taken along the cutting line C5B1 as depicted in FIG. 5B(1);

[0083] FIG. 5B(3) is a cross-sectional view taken along the cutting line C5B2 as depicted in FIG. 5B(1);

[0084] FIG. 5C(1) is a top view illustrating the structure after the dielectric layer and the capping dielectric layer are formed;

[0085] FIG. 5C(2) is a cross-sectional view taken along the cutting line C5C1 as depicted in FIG. 5C(1);

[0086] FIG. 5C(3) is a cross-sectional view taken along the cutting line C5C2 as depicted in FIG. 5C(1);

[0087] FIG. 5D(1) is a top view illustrating the structure after the fin structures are partially exposed from the gate opening;

[0088] FIG. 5D(2) is a cross-sectional view taken along the cutting line C5D1 as depicted in FIG. 5D(1);

[0089] FIG. 5D(3) is a cross-sectional view taken along the cutting line C5D2 as depicted in FIG. 5D(1);

[0090] FIG. 5E(1) is a top view illustrating the structure after the gate structures are formed;

[0091] FIG. 5E(2) is a cross-sectional view taken along the cutting line C5E1 as depicted in FIG. 5E(1); and

[0092] FIG. 5E(3) is a cross-sectional view taken along the cutting line C5E2 as depicted in FIG. 5E(1).

DETAILED DESCRIPTION OF THE DISCLOSURE

[0093] The present disclosure provides a method for forming a semiconductor device with a plurality of the MOS transistors to minimize and well control the pitch between two adjacent gate structures of two adjacent MOS transistors. The above and other aspects of the disclosure will become better understood by the following detailed description of the preferred but non-limiting embodiment(s). The following description is made with reference to the accompanying drawings:

[0094] Several embodiments of the present disclosure are disclosed below with reference to accompanying drawings. However, the structure and contents disclosed in the embodiments are for exemplary and explanatory purposes only, and the scope of protection of the present disclosure is

not limited to the embodiments. It should be noted that the present disclosure does not illustrate all possible embodiments, and anyone skilled in the technology field of the disclosure will be able to make suitable modifications or changes based on the specification disclosed below to meet actual needs without breaching the spirit of the disclosure. The present disclosure is applicable to other implementations not disclosed in the specification.

Embodiment 1

[0095] The present embodiment discloses a semiconductor device **20** having two MOS transistors **T21** and **T22** respectively formed based on two adjacent fin structures **201 F1** and **201 F2**. Detailed steps of the manufacturing method of the semiconductor device **20** are as follows: [0096] Step **S21**: A plurality of fin structures **201 F1** and **201 F2** are defined in a semiconductor substrate **201**, each of the fin structures **201F1** and **201F2** is surrounded by a fin spacer **207**; wherein Step **S21** includes Sub-steps **S211-S215**: [0097] Sub-step **S211**: A portion of the semiconductor substrate **201** are removed using a patterned pad dielectric layer **210** (including a patterned pad oxide layer **210A** and a patterned pad nitride layer **210B**) to defined the fin structures **201 F1** and **201 F2**; [0098] Sub-step **S212**: A shallow trench isolation (STIs) region **208** is formed surrounding the fin structures **201F1** and **201F2**; [0099] Sub-step **S213**: An etching back process is performed to remove portions of the shallow trench isolation (STIs) region **208**, so as to expose sidewalls of the fin structures **201 F1** and **201 F2**; and [0100] Sub-step **S214**: A thermal oxidation process is performed to form oxide spacers **207A** on the sidewalls of the fin structures **201 F1** and **201 F2**; and [0101] Sub-step **S215**: A nitride deposition process is performed to form nitride spacers **207B** on the oxide spacers **207A**; [0102] Step **S22**: Gate openings **202** are defined in a capping dielectric layer **209** covering the fin structures **201 F1** and **201 F2** and the STIs **208**, wherein the sidewalls of each of the fin structures **201F1** and **201F2** are partially exposed from corresponding one of the gate openings **202**; Step **S22** includes Sub-steps **S221-S222**: [0103] Sub-step **S221**: An oxide deposition process is performed to form the capping dielectric layer **209** on the fin structures **201 F1** and **201 F2**; [0104] Sub-step **S222**: A patterned process is performed to remove a portion of the capping dielectric layer **209** to define the gate opening **202**, from which the nitride spacers **207B** are exposed; and [0105] Sub-step **S223**: The nitride spacers **207B** and the oxide spacers **207A** within the gate opening **202** are removed, so as to make each of the fin structures **201F1** and **201F2** partially exposed from the gate opening **202**; [0106] Step **S23**: Epitaxial semiconductor material **203** (serving as a sacrificial spacer) are formed based on the exposed portions of the fin structures **201 F1** and **201 F2**; [0107] Step **S24**: The gate openings **202** are filed by an inserting dielectric layer **211** to surround the epitaxial semiconductor material **203**; [0108] Step **S25**: The epitaxial semiconductor material **203** is removed to expose the exposed portions **201 E1** and **201 E2** of the fin structures **201 F1** and **201 F2** again; and [0109] Step **S26**: gate structures **204** and **205** are formed respectively on the fin structures **201F1** and **201F2**; wherein Step **S26** includes Sub-steps **S261-S262**: [0110] Sub-step **S261**: The nitride spacers **207B** and the oxide spacers **207A** are removed to expose the fin structures **201 F1** and **201 F2**; [0111] Sub-step **S262**: Gate dielectric layers **204O** and **205O** are formed respectively covering the tops and sidewalls of the fin structures **201 F1** and **201 F2**; and [0112] Sub-step **S263**: Gate electrodes **204S** and **205S** are formed respectively covering the gate oxide layers **204O** and **205O**.

[0113] Referring to Step **S21**, a plurality of fin structures **201 F1** and **201 F2** are defined in a semiconductor substrate **201**, each of the fin structures **201 F1** and **201 F2** is surrounded by a fin spacer **207**. Referring to FIGS. **2A(1)** to **2A(3)**, FIG. **2A(1)** is a top view illustrating the structure after the fin structures **201 F1** and **201F2** are defined in the semiconductor substrate **201**; FIG. **2A(2)** is a cross-sectional view taken along the cutting line **C2A1** as depicted in FIG. **2A(1)**; and FIG. **2A(3)** is a cross-sectional view taken along the cutting line **C2A2** as depicted in FIG. **2A(1)**. The fin structures **201F1** and **201F2** are defined by Sub-Steps **S211-S215** as follows:

[0114] Referring to sub-step **S211**: An etching process using a patterned pad dielectric layer **210** (including a patterned pad oxide layer **210A** and a patterned pad nitride layer **210B**) as an etching

mask is performed to remove parts of silicon material of a semiconductor substrate **201** to create trenches **201T** and define a plurality of fin structures **201F1** and **201F2** in the semiconductor substrate **201**. In some embodiments, the distance of the adjacent two fin structures **201 F1** and **201F2** may be about 30-50 nm. Each of the fin structures **201F1** and **201F2** has a thickness about 3-10 nm, such as 5 nm.

[0115] Referring to sub-step **S212**: a shallow trench isolation (STIs) region **208** is formed surrounding the fin structures **201F1** and **201F2**. In some embodiments of the present disclosure, oxide material is deposited to fully fill the trenches **201T** and then etched back, such that the oxide material remained in the trenches **201T** can serve as STIs region **208** surrounding the plurality of fin structures **201F1** and **201F2**. Referring to Sub-step **S213**: an etching back process is performed to remove portions of the shallow trench isolation (STIs) region **408**, so as to expose sidewalls of the fin structures **201F1** and **201F2**.

[0116] Next, referring to sub-step **S214**: A thermal oxidation process is performed to form the oxide spacers **207A** on the sidewalls of the fin structures **201F1** and **201F2**; and referring to sub-step **S215**: A nitride deposition process is performed to form the nitride spacers **207B** on the oxide spacers **207A** (as shown in FIGS. **2A(2)** and **2A(3)**).

[0117] Referring to step **S22**: Gate openings **202** are defined in a capping dielectric layer **209** covering the fin structures **201 F1** and **201 F2** and the STIs region **208**, wherein the sidewalls of each of the fin structures **201 F1** and **201 F2** are partially exposed from corresponding one of the gate openings **202**; wherein Step **S22** includes Sub-steps **S221-S222**:

[0118] Referring to Sub-step **S221**: An oxide deposition process is performed to form the capping dielectric layer **209** on the fin structures **201 F1** and **201 F2**. See FIGS. **2B(1)** to **2B(3)**, FIG. **2B(1)** is a top view illustrating the structure after the capping dielectric layer **209** is formed to cover the fin structures **201 F1** and **201 F2**; FIG. **2B(2)** is a cross-sectional view taken along the cutting line **C2B1** as depicted in FIG. **2B(1)**; and FIG. **2B(3)** is a cross-sectional view taken along the cutting line **C2B2** as depicted in FIG. **2B(1)**. In the present embodiment, the oxide deposition process for forming the capping dielectric layer **209** is followed by a planarization process; and the capping dielectric layer **209** includes silicon dioxide (SiO₂).

[0119] Referring to Sub-step **S222**: a patterned process is performed to remove a portion of the capping dielectric layer **209** to define the gate opening **202**, from which the nitride spacers **207B** are exposed. Referring to Sub-step **S223**: the nitride spacers **207B** and the oxide spacers **207A** are then removed respectively by another etching process, so as to make each of the fin structures **201 F1** and **201 F2** partially exposed from the gate opening **202**. See FIGS. **2C(1)** to **2C(3)**, FIG. **2C(1)** is a top view illustrating the structure after the fin structures **201 F1** and **201 F2** are partially exposed from the gate opening **202**; FIG. **2C(2)** is a cross-sectional view taken along the cutting line **C2C1** as depicted in FIG. **2C(1)**; and FIG. **2C(3)** is a cross-sectional view taken along the cutting line **C2B2** as depicted in FIG. **2C(1)**.

[0120] Referring to Step **S23**: Epitaxial semiconductor material **203** (serving as a sacrificial spacer) are formed based on the exposed portions of the fin structures **401 F1** and **201 F2**. See FIGS. **2D(1)** and **2D(2)**, wherein FIG. **2D(1)** is a top view illustrating the structure after the epitaxial semiconductor material **203** is formed; and FIG. **2D(2)** is a cross-sectional view taken along the cutting line **C2D1** as depicted in FIG. **2D(1)**. In some embodiments of the present disclosure, the epitaxial semiconductor material **203** (such as Si, SiGe, Ge, etc.) is formed by a selective epitaxy growth (SEG) method based on the exposed portions of the fin structures **201F1** and **201F2**. In some other embodiments of the present disclosure, depending on the material of the fin structures other semiconductor epitaxial material (such as, SiC, gallium arsenide (GaAs), gallium nitride (GaN), etc.) may be grown based on the exposed portions of the fin structures **201F1** and **201F2**. The epitaxial semiconductor material **203** has a thickness about 5-12 nm, such as 7-8 nm.

[0121] Next, referring to Step **S24**: The gate opening **202** is filed by an inserting dielectric layer **211**. See FIGS. **2E(1)** and **2E(2)**. FIG. **2E(1)** is a top view illustrating the structure after the gate

opening **202** is filled by an inserting dielectric layer **211**; and FIG. 2E(2) is a cross-sectional view taken along the cutting line C2E1 as depicted in FIG. 2E(1). In some embodiments of the present disclosure, the material constituting the inserting dielectric layer **211** may be different from that constituting the capping dielectric layer **209**. In the present embodiment, the inserting dielectric layer **211** is formed by a low-k dielectric material (such as, SiCOH) deposition process. The inserting dielectric layer **211** may be then etched back. Such that, the patterned pad nitride layer **210B** (or even the pad oxide layer **210A**) can be exposed from the partially filled gate opening **202**. Moreover, as shown in FIG. 2E(2), the distance D2 between two epitaxial semiconductor material **203** or sacrificial spacers is around 15-30 nm, such as 20 nm, and the distance D2 could be equal to or substantially equal to the “gate cut” or “poly cut” distance between two gate structures of the adjacent transistors.

[0122] Referring to Steps S25: The epitaxial semiconductor material **203** is removed to form vacancies and expose the sidewalls of the fin structures **201 F1** and **201 F2** again; and then referring to Step S26: Gate structures **204** and **205** are formed respectively on the fin structures **201 F1** and **201 F2**. See FIGS. 2F(1) and 2F(2). FIG. 2F(1) is a top view illustrating the structure after the gate structures **204** and **205** are formed; FIG. 2F(2) is a cross-sectional view taken along the cutting line C2F1 as depicted in FIG. 2F(1); and FIG. 2F(3) is a cross-sectional view taken along the cutting line C2F2 as depicted in FIG. 2F(1).

[0123] The Step S26 for forming the gate structures **204** and **205** includes Sub-steps S261-S262: Referring to Sub-step S461: The nitride spacers **207B** and the oxide spacers **207A** are removed to expose the fin structures **201 F1** and **201F2**. In the present embodiments, the nitride spacers **207B** and the oxide spacers **207A** are removed by different etching processes respectively.

[0124] Next, referring to Sub-step S262: The gate dielectric layers **204O** and **205O** are formed respectively covering the tops and sidewalls of the fin structures **201F1** and **201F2**. In some embodiments of the present disclosure, the gate dielectric layers **204O** and **205O** are formed by an oxide deposition process. Then, referring to Sub-step S263: The gate electrodes **204S** and **205S** are formed respectively covering the gate dielectric layers **204O** and **205O**. In some embodiments of the present disclosure, the gate electrodes **204S** and **205S** are formed by polysilicon or metal. Thus, the vacancies formed after the epitaxial semiconductor material **203** is removed are just be filled with the gate dielectric layers **204O** and **205O** and the gate electrodes **204S** and **205S**.

[0125] After the forming of the gate structures **204** and **205**, the source/drain regions for the transistors could be formed. For example, remove portion of fin structures outside the gate regions, localized isolations **215** and **225** are (optionally) then formed in the semiconductor substrate **201**. The source region **212** including an LDD region (e.g. N⁻ semiconductor region) **212A**, a N⁺ semiconductor region **212B** and a landing pad **212C**, as well as the drain region **213** including an LDD region (e.g. N⁻ semiconductor region) **213A**, a N⁺ semiconductor region **213B** and a landing pad **213C** are formed over the localized isolations **215** and electrically contact to the fin structure **201F1**, wherein the landing pads **212C** (or **213C**) may contact the most lateral sidewall of the N⁺ semiconductor region **212B** (or **213B**). Similarly, the source region **222** including an LDD region (e.g. N⁻ semiconductor region) **222A**, a N⁺ semiconductor region **222B** and a landing pad **222C**, as well as the drain region **223** including an LDD region (e.g. N⁻ semiconductor region) **223A**, a N⁺ semiconductor region **223B** and a landing pad **223C** are formed over the localized isolations **225** and electrically contact to the fin structure **201 F2**. Such that, the semiconductor device **20** (see FIG. 2G) with two adjacent MOS transistors **T21** and **T22** are formed and separated from each other for a certain gate electrode pitch P2 (or called as “gate cut” distance or “poly cut” distance), wherein the gate electrode pitch P2 can be equal to the certain distance D2 that is defined by the portion of the dielectric material **211** disposed between the two adjacent fin structures **201 F1** and **201 F2**.

[0126] After a series steps of down-stream process are performed, the forming of the semiconductor device **20** (such as, a SRAM cell) applying the MOS transistors **T21** and **T22** can be

implemented. Since, the certain distance D2 can be well controlled by the dielectric material **211** deposited into the gate opening **202**, which is far less than the traditional lithography rule used to define the gate electrode pitch of two adjacent MOS transistors, thus the gate electrode pitch P2 between two adjacent MOS transistors T21 and T22 can be significant minimized.

[0127] In addition, since the fin structures **201F1** and **201F2** can be protected by the fin spacer **207** prior to gate and source/drain formation, and be well supported by the first dielectric material **209**, thus it can prevent the fin structures **201F1** and **201F2** from been collapsed during the process for forming the gate structures **204** and **205**, the source region **212/222** and the drain region **213/223**.
Embodiment 2

[0128] The present embodiment discloses another semiconductor device **30** having two MOS transistors T31 and T32 respectively formed based on two adjacent fin structures **301 F1** and **301 F2**. Detailed steps of the manufacturing method of the semiconductor device **30** are as follows:

[0129] Step S31: A plurality of fin structures **301 F1** and **301 F2** are defined in a semiconductor substrate **301**, each of the fin structures **301F1** and **301F2** is surrounded by a fin spacer **307**; wherein Step S31 includes Sub-steps S311-S313: [0130] Sub-step S311: A portion of the semiconductor substrate **301** are removed using a patterned pad dielectric layer **310** (including a patterned pad oxide layer **310A** and a patterned pad nitride layer **310B**) to defined the fin structures **301 F1** and **301 F2**; [0131] Sub-step S312: A shallow trench isolation (STIs) **308** is formed surrounding the fin structures **301 F1** and **301 F2**; [0132] Sub-step S313: An etching back process is performed to remove portions of the shallow trench isolation (STIs) **308**, so as to expose sidewalls of the fin structures **301 F1** and **301 F2**; and [0133] Sub-step S314: A thermal oxidation process is performed to form oxide spacers **307A** on the sidewalls of the fin structures **301 F1** and **301 F2**; [0134] Sub-step S315: A nitride deposition process is performed to form nitride spacers **307B** on the oxide spacers **307A**; and [0135] Sub-step S316: Amorphous silicon spacers **307C** (serving as a sacrificial spacer) are formed on the nitride spacers **307B**; [0136] Step S32: Gate openings **302** are defined in a capping dielectric layer **309** covering the fin structures **301 F1** and **301 F2** and the STIs **308**, wherein the sidewalls of each of the fin structures **301F1** and **301F2** are partially exposed from corresponding one of the gate openings **302**. Step S32 includes Sub-steps S321-S324: [0137] Sub-step S321: An inserting dielectric layer **311** is formed to surround the sidewalls of the fin structures **301 F1** and **301 F2**; [0138] Sub-step S322: An oxide deposition process is performed to form the capping dielectric layer **309** on the fin structures **301F1** and **301F2** and the inserting dielectric layer **311**; [0139] Sub-step S323: A patterned process is performed to remove a portion of the capping dielectric layer **309** to define the gate opening **302**; and [0140] Sub-step S324: the amorphous silicon spacers **307C**, the nitride spacers **307B** and the oxide spacers **307A** are removed, so as to make each of the fin structures **301F1** and **301F2** partially exposed from the gate opening **302**; [0141] Step S33: Gate structures **304** and **305** are formed respectively on the fin structures **301F1** and **301F2**; wherein Step S33 includes Sub-steps S331-S332: [0142] Sub-step S331: Gate dielectric layers **3040** and **3050** are formed respectively covering the tops and sidewalls of the fin structures **301 F1** and **301 F2**; and [0143] Sub-step S332: Gate electrodes **304S** and **305S** are formed respectively covering the gate oxide layers **3040** and **3050**.

[0144] Referring to Step S31, a plurality of fin structures **301 F1** and **301F2** are defined in a semiconductor substrate **301**, each of the fin structures **301 F1** and **301F2** is surrounded by a fin spacer **307**. See FIGS. 3A(1) to 3A(3), FIG. 3A(1) is a top view illustrating the structure after the fin structures **301 F1** and **301F2** are defined in the semiconductor substrate **301**; FIG. 3A(2) is a cross-sectional view taken along the cutting line C3A1 as depicted in FIG. 3A(1); and FIG. 3A(3) is a cross-sectional view taken along the cutting line C3A2 as depicted in FIG. 3A(1). The fin structures **301F1** and **301F2** are defined by Sub-Steps S311-S315 as follows:

[0145] Referring to sub-step S311: An etching process, using a patterned pad dielectric layer **310** (including a patterned pad oxide layer **310A** and a patterned pad nitride layer **310B**) as an etching

mask, is performed to remove parts of silicon material of a semiconductor substrate **301** to create trenches **301T** and define a plurality of fin structures **301F1** and **301F2** in the semiconductor substrate **301**. In some embodiments, the distance of the adjacent two fin structures **301 F1** and **301 F2** may be about 30-50 nm. Each of the fin structures **301F1** and **301F2** has a thickness about 3-10 nm, such as 5 nm.

[0146] Referring to sub-step **S312**: a shallow trench isolation (STIs) **308** is formed surrounding the fin structures **301F1** and **301F2**. In some embodiments of the present disclosure, oxide material is deposited to fully fill the trenches **301T** and then etched back, such that the oxide material remained in the trenches **301T** can serve as STIs **308** surrounding the plurality of fin structures **301F1** and **301F2**. Referring to Sub-step **S313**: An etching back process is performed to remove portions of the shallow trench isolation (STI) regions **308**, so as to expose sidewalls of the fin structures **301 F1** and **301 F2**.

[0147] Next, referring to sub-step **S314**: A thermal oxidation process is performed to form the oxide spacers **307A** on the sidewalls of the fin structures **301F1** and **301F2**. Then referring to sub-step **S315**: A nitride deposition process is performed to form the nitride spacers **307B** on the oxide spacers **307A**. And referring to sub-step **S316**: Amorphous silicon spacers **307C** (serving as a sacrificial spacer) are formed on the nitride spacers **307B**. In some embodiments of the present disclosure, the forming of the amorphous silicon spacers **307C** includes steps of depositing amorphous silicon to cover the fin spacer **307**, the shallow trench isolation (STIs) **308** and the fin structures **301 F1** and **301 F2**; and performing an anisotropic etching process to removing portions of the amorphous silicon and to remain the portion of the amorphous silicon disposed on the sidewalls of the nitride spacers **307B**. Each of the amorphous silicon spacers **307C** has a thickness about 5-10 nm.

[0148] Referring to step **S32**: Gate openings **302** are defined in a capping dielectric layer **309** covering the fin structures **301 F1** and **301 F2** and the STIs **308**, wherein the sidewalls of each of the fin structures **301 F1** and **301 F2** are partially exposed from corresponding one of the gate openings **302**. Wherein Step **S32** includes Sub-steps **S321-S324**:

[0149] Referring to Sub-step **S321**: An inserting dielectric layer **311** is formed to surround the sidewalls of the fin structures **301 F1** and **301 F2**, and referring to Sub-step **S322**: An oxide deposition process is performed to form the capping dielectric layer **309** on the fin structures **301 F1** and **301 F2** and the inserting dielectric layer **311**. See FIGS. **3B(1)** to FIG. **3B(3)**, FIG. **3B(1)** is a top view illustrating the structure after the inserting dielectric layer **311** and the capping dielectric layer **309** are formed; FIG. **3B(2)** is a cross-sectional view taken along the cutting line **C3B1** as depicted in FIG. **3B(1)**; and FIG. **3B(3)** is a cross-sectional view taken along the cutting line **C2B2** as depicted in FIG. **3B(1)**.

[0150] In some embodiments of the present disclosure, the material constituting the inserting dielectric layer **311** may be different from that constituting the capping dielectric layer **309**. In the present embodiment, the inserting dielectric layer **311** is formed by a low-k dielectric material (such as, SiCOH) deposition process to filling in the trenches **301T**. The deposited low-k dielectric material may be planarized by a chemical-mechanical polishing (CMP), and then etched backed by using the pad nitride layer **310B**, nitride spacers **307B** and the amorphous silicon spacers **307C** as an etching stop layer. Such that, the pad nitride layer **310B**, nitride spacers **307B** and the amorphous silicon spacers **307C** can be exposed from the partially filled trenches **301T**. Sub-step **S322**: the oxide deposition process for forming the capping dielectric layer **309** includes depositing SiO₂ to cover the pad nitride layer **310B**, nitride spacers **307B** and the amorphous silicon spacers **307C**, and is followed by a planarization process (such as, CMP).

[0151] Referring to Sub-step **S323**: A patterned process is performed to remove a portion of the capping dielectric layer **309** to define the gate opening **302**. In some embodiment, a patterned photoresist layer (not shown) is formed on the capping dielectric layer **309** to expose the portion of the capping dielectric layer **309** covering the fin structures **301F1** and **301 F2**. Then, an etching

process is performed to remove the exposed portion of the capping dielectric layer **309** to define the gate opening **302** in the capping dielectric layer **309**.

[0152] Referring to Sub-step S324: the amorphous silicon spacers **307C**, the nitride spacers **307B** and the oxide spacers **307A** are removed, so as to make each of the fin structures **301F1** and **301F2** partially exposed from the gate opening **302**. See FIGS. 3C(1) to FIG. 3C(3), FIG. 3C(1) is a top view illustrating the structure after the fin structures **301F1** and **301F2** are partially exposed from the gate opening **302**; FIG. 3C(2) is a cross-sectional view taken along the cutting line C3C1 as depicted in FIG. 3C(1); and FIG. 3C(3) is a cross-sectional view taken along the cutting line C3C2 as depicted in FIG. 3C(1).

[0153] In the present embodiment, after the gate opening **302** is defined in the capping dielectric layer **309**, another etching process is then performed to remove the amorphous silicon spacers **307C**. After the patterned photoresist layer is peered, yet another process is performed remove the nitride spacers **307B** and the portion of the patterned pad nitride **310B** from the gate opening **302**. Next, the oxide spacers **307A** and the portion of the patterned pad oxide layer **310A** exposed from the gate opening **302** are removed by another etching process, so as to expose the tops and sidewalls of each fin structures **301F1** and **301F2**.

[0154] Referring to Steps S33: Gate structures **304** and **305** are formed respectively on the fin structures **301F1** and **301F2**. See FIGS. 3D(1) to 3D(3). FIG. 3D(1) is a top view illustrating the structure after the gate structures **304** and **305** are formed; FIG. 3D(2) is a cross-sectional view taken along the cutting line C3E1 as depicted in FIG. 3D(1); and FIG. 3D(3) is a cross-sectional view taken along the cutting line C3D2 as depicted in FIG. 3D(1).

[0155] The Step S33 for forming the gate structures **304** and **305** includes Sub-steps S331-S332: Referring to Sub-step S331: The gate dielectric layers **3040** and **3050** are formed respectively covering the tops and sidewalls of the fin structures **301F1** and **301F2**. In some embodiments of the present disclosure, the gate dielectric layers **3040** and **3050** are formed by an oxide deposition process. Then, referring to Sub-step S332: The gate electrodes **304S** and **305S** are formed respectively covering the gate dielectric layers **3040** and **3050**. In some embodiments of the present disclosure, the gate electrodes **304S** and **305S** are formed by polysilicon or metal.

[0156] After the forming of the gate structures **304** and **305**, the capping dielectric layer **309** is then removed, and the source/drain regions could be formed as previously mentioned. Again, since the certain distance can be well controlled by the second dielectric material of the inserting dielectric layer **311** deposited in the gate opening **302**, which is far less than the traditional lithography rule used to define the gate electrode pitch of two adjacent MOS transistors, thus the gate electrode pitch between two adjacent MOS transistors T31 and T32 can be significant minimized.

[0157] In addition, since the sidewalls of the fin structures **301F1** and **301F2** can be protected by the fin spacer **307** prior to gate and source/drain formation, and be well supported by the first dielectric material of the capping dielectric layer **309** and the second dielectric material of the inserting dielectric layer **311**, thus it can prevent the vulnerable fin structures **301F1** and **301F2** from been collapsed during the process for forming the gate structures **304** and **305**, the source region **312/322** and the drain region **313/323**.

Embodiment 3

[0158] The present embodiment discloses a semiconductor device **40** having two MOS transistors T41 and T42 respectively formed based on two adjacent fin structures **401F1** and **401F2**. Detailed steps of the manufacturing method of the semiconductor device **40** are as follows: [0159] Step S41: A plurality of fin structures **401F1** and **401F2** are defined in a semiconductor substrate **401**, each of the fin structures **401F1** and **401F2** is surrounded by a fin spacer **407**; wherein Step S41 includes Sub-steps S411-S415: [0160] Sub-step S411: A portion of the semiconductor substrate **401** are removed using a patterned pad dielectric layer **410** (including a patterned pad oxide layer **410A** and a patterned pad nitride layer **410B**) to defined the fin structures **401F1** and **401F2**; [0161] Sub-step S412: A shallow trench isolation (STIs) region **408** is formed surrounding the fin structures

401F1 and **401 F2**; [0162] Sub-step **S413**: An etching back process is performed to remove portions of the shallow trench isolation (STI) regions **408**, so as to expose sidewalls of the fin structures **401 F1** and **401 F2**; and [0163] Sub-step **S414**: A thermal oxidation process is performed to form oxide spacers **407A** on the sidewalls of the fin structures **401 F1** and **401 F2**; and [0164] Sub-step **S415**: A nitride deposition process is performed to form nitride spacers **407B** on the oxide spacers **407B**; [0165] Step **S42**: Gate openings **402** are defined in a capping dielectric layer **409** covering the fin structures **401 F1** and **401 F2** and the STIs **408**, wherein the sidewalls of each of the fin structures **401F1** and **401F2** are partially exposed from corresponding one of the gate openings **402**; wherein Step **S42** includes Sub-steps **S421-S422**: [0166] Sub-step **S421**: An oxide deposition process is performed to form the capping dielectric layer **409** on the fin structures **401 F1** and **401 F2**; [0167] Sub-step **S422**: An patterned process is performed to remove a portion of the capping dielectric layer **409** to define the gate opening **402**, from which the nitride spacers **407B** are exposed; and [0168] Sub-step **S423**: The nitride spacers **407B** and the oxide spacers **407B** within the gate opening **402** are removed, so as to make each of the fin structures **401F1** and **401F2** partially exposed from the gate opening **402**; [0169] Step **S43**: Epitaxial semiconductor material **403** (serving as a sacrificial spacer) are formed based on the exposed portions of the fin structures **401 F1** and **401 F2**; [0170] Step **S44**: The gate openings **402** are deepen by etching the STI region **408** therein to expose the semiconductor substrate **401**; [0171] Step **S45**: The gate openings **402** are filed by an inserting dielectric layer **411** to surround the epitaxial semiconductor material **403**; [0172] Step **S46**: The epitaxial semiconductor material **403** is removed to expose the exposed portions **401E1** and **401E2** of the fin structures **401F1** and **401F2** again; and [0173] Step **S47**: gate structures **404** and **405** are formed respectively on the fin structures **401F1** and **401F2**.

[0174] Referring to Step **S41**, a plurality of fin structures **401F1** and **401F2** are defined in a semiconductor substrate **401**, each of the fin structures **401 F1** and **401F2** is surrounded by a fin spacer **407**. Referring to FIGS. **4A(1)** to **4A(3)**, FIG. **4A(1)** is a top view illustrating the structure after the fin structures **401F1** and **401F2** are defined in the semiconductor substrate **401**; FIG. **4A(2)** is a cross-sectional view taken along the cutting line **C4A1** as depicted in FIG. **4A(1)**; and FIG. **4A(3)** is a cross-sectional view taken along the cutting line **C4A2** as depicted in FIG. **4A(1)**. The fin structures **401F1** and **401F2** are defined by Sub-Steps **S411-S415** as follows:

[0175] Referring to sub-step **S411**: An etching process using a patterned pad dielectric layer **410** (including a patterned pad oxide layer **410A** and a patterned pad nitride layer **410B**) as an etching mask is performed to remove parts of silicon material of a semiconductor substrate **401** to create trenches **401T** and define a plurality of fin structures **401F1** and **401F2** in the semiconductor substrate **401**. In some embodiments, the distance of the adjacent two fin structures **401F1** and **401F2** may be about 30-50 nm. Each of the fin structures **401F1** and **401F2** has a thickness about 3-10 nm, such as 5 nm.

[0176] Referring to sub-step **S412**: a shallow trench isolation (STI) regions **408** is formed surrounding the fin structures **401F1** and **401F2**. In some embodiments of the present disclosure, oxide material is deposited to fully fill the trenches **401T** and then etched back, such that the oxide material remained in the trenches **401T** can serve as STI regions **408** surrounding the plurality of fin structures **401F1** and **401F2**. Referring to Sub-step **S413**: an etching back process is performed to remove portions of the shallow trench isolation (STI) regions **408**, so as to expose sidewalls of the fin structures **401F1** and **401F2**.

[0177] Next, referring to sub-step **S414**: A thermal oxidation process is performed to form the oxide spacers **407A** on the sidewalls of the fin structures **401 F1** and **401 F2**; and referring to sub-step **S415**: A nitride deposition process is performed to form the nitride spacers **407B** on the oxide spacers **407A** (as shown in FIGS. **4A(2)** and **4A(3)**).

[0178] Referring to step **S42**: Gate openings **402** are defined in a capping dielectric layer **409** covering the fin structures **401F1** and **401F2** and the STIs **408**, wherein the sidewalls of each of the fin structures **401F1** and **401F2** are partially exposed from corresponding one of the gate openings

402; wherein Step **S42** includes Sub-steps **S421-S422**:

[0179] Referring to Sub-step **S421**: An oxide deposition process is performed to form the capping dielectric layer **209** on the fin structures **201F1** and **401F2**. See FIGS. **4B(1)** to **4B(3)**, FIG. **4B(1)** is a top view illustrating the structure after the capping dielectric layer **409** is formed to cover the fin structures **401F1** and **401F2**; FIG. **4B(2)** is a cross-sectional view taken along the cutting line **C4B1** as depicted in FIG. **4B(1)**; and FIG. **4B(3)** is a cross-sectional view taken along the cutting line **C2B2** as depicted in FIG. **4B(1)**. In the present embodiment, the oxide deposition process for forming the capping dielectric layer **409** is followed by a planarization process; and the capping dielectric layer **409** includes SiO₂.

[0180] Referring to Sub-step **S422**: a patterned process is performed to remove a portion of the capping dielectric layer **209** to define the gate opening **402**, from which the nitride spacers **407B** are exposed. Referring to Sub-step **S423**: the nitride spacers **407B** and the oxide spacers **407A** are then removed respectively by another etching process, so as to make each of the fin structures **401F1** and **401F2** partially exposed from the gate opening **402**. See FIGS. **4C(1)** to **4C(3)**, FIG. **4C(1)** is a top view illustrating the structure after the fin structures **401F1** and **401F2** are partially exposed from the gate opening **402**; FIG. **4C(2)** is a cross-sectional view taken along the cutting line **C4C1** as depicted in FIG. **4C(1)**; and FIG. **4C(3)** is a cross-sectional view taken along the cutting line **C4B2** as depicted in FIG. **4C(1)**.

[0181] Referring to Step **S43**: Epitaxial semiconductor material **403** (serving as a sacrificial spacer) are formed based on the exposed portions of the fin structures **401F1** and **401F2**. See FIGS. **4D(1)** and **4D(2)**, wherein FIG. **4D(1)** is a top view illustrating the structure after the epitaxial semiconductor material **403** is formed; and FIG. **4D(2)** is a cross-sectional view taken along the cutting line **C4D1** as depicted in FIG. **4D(1)**. In some embodiments of the present disclosure, the epitaxial semiconductor material **403** (such as Si, SiGe, Ge, etc.) is formed by a SEG method based on the exposed portions of the fin structures **401F1** and **401F2**. In some other embodiments of the present disclosure, other semiconductor epitaxial material (such as, GaAs, GaN, SiC, etc.) may be grown based on the exposed portions of the fin structures **401F1** and **401F2**. The epitaxial semiconductor material **403** has a thickness about 5-12 nm, such as 7-8 nm.

[0182] Next, referring to Step **S44**: The gate openings **402** are deepen to expose the semiconductor substrate **401**. See FIGS. **4E(1)** and **4E(2)**. FIG. **4E(1)** is a top view illustrating the structure after the gate openings **402** are deepen to expose the semiconductor substrate **401**; and FIG. **4E(2)** is a cross-sectional view taken along the cutting line **C4E1** as depicted in FIG. **4E(1)**. In some embodiments of the present disclosure, an etching process is performed to remove the portion of the STI regions **408** exposed from the gate opening **402** and the portion of the semiconductor substrate **401** beneath the removed portion of the STIs **408**.

[0183] Thereinafter, referring to Step **S45**: The gate openings **402** are filed by an inserting dielectric layer **411** to surround the epitaxial semiconductor material **403** and the remained STIs **408**. See FIGS. **4F(1)** and **4F(2)**. FIG. **4F(1)** is a top view illustrating the structure after the gate opening **402** is filed by an inserting dielectric layer **411**; and FIG. **4F(2)** is a cross-sectional view taken along the cutting line **C4F1** as depicted in FIG. **4F(1)**. In some embodiments of the present disclosure, the material constituting the inserting dielectric layer **411** may be different from that constituting the capping dielectric layer **409**. In the present embodiment, the inserting dielectric layer **411** is formed by a low-k dielectric material (such as, SiCOH) deposition process. The bottom of the inserting dielectric layer **411** (SiCOH) is lower than the bottom of the STIs **408**. Since the dielectric constant of the inserting dielectric layer **411** (SiCOH) is lower than that of the STIs **408**, therefore, the coupling effect between two gate structures **404** and **406** (which will be formed later, see FIGS. **4G(1)** to **4G(3)**) could be improved. The inserting dielectric layer **411** may be then etched back. Such that, the patterned pad nitride layer **410B** can be exposed from the partially filled gate opening **402**. Moreover, as shown in FIG. **4F(2)**, the distance **D4** between two epitaxial semiconductor material **403** or sacrificial spacers is around 15-30 nm, such as 20 nm, and the

distance **D4** could be equal to or substantially equal to the “gate cut” or “poly cut” distance between two gate structures of the adjacent transistors. The distance **D4** could be equal to the width of the inserting dielectric layer **411** between the fin structures **401F1** and **401F2**.

[0184] Referring to Steps **S46**: The epitaxial semiconductor material **403** is removed to form vacancies and expose the sidewalls of the fin structures **401F1** and **401F2** again; and then referring to Step **S47**: Gate structures **404** and **405** are formed respectively on the fin structures **401F1** and **401F2**. See FIGS. **4G(1)** to **4G(3)**. FIG. **4G(1)** is a top view illustrating the structure after the gate structures **404** and **405** are formed; FIG. **4G(2)** is a cross-sectional view taken along the cutting line **C4G1** as depicted in FIG. **4G(1)**; and FIG. **4G(3)** is a cross-sectional view taken along the cutting line **C4G2** as depicted in FIG. **4G(1)**.

[0185] The Step **S47** for forming the gate structures **404** and **405** includes Sub-steps **S471-S473**: Referring to Sub-step **S471**: The nitride spacers **407B** and the oxide spacers **407A** are removed to expose the fin structures **401 F1** and **401F2**. In the present embodiments, the nitride spacers **407B** and the oxide spacers **407A** are removed by different etching processes respectively.

[0186] Next, referring to Sub-step **S472**: The gate dielectric layers **4040** and **4050** are formed respectively covering the tops and sidewalls of the fin structures **401 F1** and **401 F2**. In some embodiments of the present disclosure, the gate dielectric layers **4040** and **4050** are formed by an oxide deposition process. Then, referring to Sub-step **S473**: The gate electrodes **404S** and **405S** are formed respectively covering the gate dielectric layers **4040** and **4050**. In some embodiments of the present disclosure, the gate electrodes **404S** and **405S** are formed by polysilicon or metal. Thus, the vacancies formed after the epitaxial semiconductor material **403** is removed are just be filled with the gate dielectric layers **4040** and **4050** and the gate electrodes **204S** and **205S**.

[0187] After the forming of the gate structures **404** and **405**, the source/drain regions for the transistors could be formed as previously mentioned.

[0188] Compared with Embodiment I, in the present embodiment, between two gate structures **404** and **405**, the bottom of the inserting dielectric layer **411** (**SiCOH**) is lower than the bottom of the STIs **408**. Since the dielectric constant of the inserting dielectric layer **411** (**SiCOH**) is lower than that of the STI region **408**, therefore, the coupling effect between two gate structures **404** and **405** could be improved.

Embodiment 4

[0189] The present embodiment discloses another semiconductor device **50** having two MOS transistors **T51** and **T52** respectively formed based on two adjacent fin structures **501F1** and **501F2**. Detailed steps of the manufacturing method of the semiconductor device **30** are as follows: [0190] Step **S51**: A plurality of fin structures **501F1** and **501F2** are defined in a semiconductor substrate **501**, each of the fin structures **501F1** and **501F2** is surrounded by a fin spacer **507**; wherein Step **S51** includes Sub-steps **S511-S513**: [0191] Sub-step **S511**: A portion of the semiconductor substrate **501** are removed using a patterned pad dielectric layer **510** (including a patterned pad oxide layer **510A** and a patterned pad nitride layer **510B**) to define the fin structures **501F1** and **501F2**; [0192] Sub-step **S512**: A shallow trench isolation (STI) regions **508** is formed surrounding the fin structures **501F1** and **501F2**; [0193] Sub-step **S513**: An etching back process is performed to remove portions of the shallow trench isolation (STI) regions **508**, so as to expose sidewalls of the fin structures **501F1** and **501F2**; and [0194] Sub-step **S514**: A thermal oxidation process is performed to form oxide spacers **507A** on the sidewalls of the fin structures **501F1** and **501F2**; [0195] Sub-step **S515**: A nitride deposition process is performed to form nitride spacers **507B** on the oxide spacers **507A**; and [0196] Sub-step **S516**: Amorphous silicon spacers **507C** (serving as a sacrificial spacer) are formed on the nitride spacers **507B**; [0197] Step **S52**: The portion of the STIs **508** not covered by the fin spacers **507** (including oxide spacers **507A**, the nitride spacers **507B** and the amorphous silicon spacers **507C**) is removed to expose the portion of the semiconductor substrate **501** beneath the removed portion of the STIs **508**; [0198] Step **S53**: Gate opening **502** is defined in a capping dielectric layer **509** covering the fin structures **501F1** and **501F2** and the STIs

508, wherein the sidewalls of each of the fin structures **501F1** and **501F2** are partially exposed from corresponding one of the gate openings **502**; wherein Step **S53** includes Sub-steps **S531-S534**: [0199] Sub-step **S531**: An inserting dielectric layer **511** is formed to surround the sidewalls of the fin structures **501F1** and **501F2**; [0200] Sub-step **S532**: An oxide deposition process is performed to form the capping dielectric layer **509** on the fin structures **501F1** and **501F2** and the inserting dielectric layer **511**; [0201] Sub-step **S533**: A patterned process is performed to remove a portion of the capping dielectric layer **509** to define the gate opening **502**; and [0202] Sub-step **S534**: the amorphous silicon spacers **507C**, the nitride spacers **507B** and the oxide spacers **507A** are removed, so as to make each of the fin structures **501F1** and **501F2** partially exposed from the gate opening **502**; [0203] Step **S54**: Gate structures **504** and **505** are formed respectively on the fin structures **501F1** and **501F2**; wherein Step **S54** includes Sub-steps **S541-S542**: [0204] Sub-step **S541**: Gate dielectric layers **504O** and **505O** are formed respectively covering the tops and sidewalls of the fin structures **501F1** and **501F2**; and [0205] Sub-step **S542**: Gate electrodes **504S** and **505S** are formed respectively covering the gate oxide layers **504O** and **505O**.

[0206] Referring to Step **S51**, a plurality of fin structures **501F1** and **501F2** are defined in a semiconductor substrate **501**, each of the fin structures **501F1** and **501F2** is surrounded by a fin spacer **507**. See FIGS. 5A(1) to 5A(3), FIG. 5A(1) is a top view illustrating the structure after the fin structures **501F1** and **501F2** are defined in the semiconductor substrate **501**; FIG. 5A(2) is a cross-sectional view taken along the cutting line C5A1 as depicted in FIG. 5A(1); and FIG. 5A(3) is a cross-sectional view taken along the cutting line C5A2 as depicted in FIG. 5A(1). The fin structures **501F1** and **501F2** are defined by Sub-Steps **S511-S515** as follows:

[0207] Referring to sub-step **S511**: An etching process, using a patterned pad dielectric layer **510** (including a patterned pad oxide layer **510A** and a patterned pad nitride layer **510B**) as an etching mask, is performed to remove parts of silicon material of a semiconductor substrate **501** to create trenches **501T** and define a plurality of fin structures **501F1** and **501F2** in the semiconductor substrate **501**. In some embodiments, the distance of the adjacent two fin structures **501F1** and **501F2** may be about 30-50 nm. Each of the fin structures **501F1** and **501F2** has a thickness about 3-10 nm, such as 5 nm.

[0208] Referring to sub-step **S512**: a shallow trench isolation (STIs) **508** is formed surrounding the fin structures **501F1** and **501F2**. In some embodiments of the present disclosure, oxide material is deposited to fully fill the trenches **501T** and then etched back, such that the oxide material remained in the trenches **501T** can serve as the STIs **508** surrounding the plurality of fin structures **501F1** and **501F2**. Referring to Sub-step **S513**: An etching back process is performed to remove portions of the shallow trench isolation (STI) regions **508**, so as to expose sidewalls of the fin structures **501F1** and **501F2**.

[0209] Next, referring to sub-step **S514**: A thermal oxidation process is performed to form the oxide spacers **307A** on the sidewalls of the fin structures **501F1** and **501F2**. Then referring to sub-step **S515**: A nitride deposition process is performed to form the nitride spacers **507B** on the oxide spacers **507A**. And referring to sub-step **S516**: Amorphous silicon spacers **507C** (serving as a sacrificial spacer) are formed on the nitride spacers **507B**. In some embodiments of the present disclosure, the forming of the amorphous silicon spacers **507C** includes steps of depositing amorphous silicon to cover the fin spacer **507**, the shallow trench isolation (STIs) **508** and the fin structures **501F1** and **501F2**; and performing an anisotropic etching process to removing portions of the amorphous silicon and to remain the portion of the amorphous silicon disposed on the sidewalls of the nitride spacers **507B**. Each of the amorphous silicon spacers **507C** has a thickness about 5-10 nm.

[0210] Referring to step **S52**: The portion of the STI regions **508** not covered by the fin spacers **507** (including oxide spacers **507A**, the nitride spacers **507B** and the amorphous silicon spacers **507C**) is removed to expose the portion of the semiconductor substrate **501** beneath the removed portion of the STI regions **508**. See FIGS. 5B(1) to 5B(3), FIG. 5B(1) is a top view illustrating the structure

after the portion of the STIs **508** not covered by the fin spacers **507** is removed; FIG. **5B(2)** is a cross-sectional view taken along the cutting line **C5B1** as depicted in FIG. **5B(1)**; and FIG. **5B(3)** is a cross-sectional view taken along the cutting line **C5B2** as depicted in FIG. **5B(1)**.

[0211] In the present embodiment, a portion of the semiconductor substrate **501** beneath the removed portion of the STIs **508** can be also removed, so as to make the top surface of the remaining portion of the semiconductor substrate **501** is lower than the bottom of the remained STI regions **508**.

[0212] Referring to step **S53**: Gate opening **502** is defined in a capping dielectric layer **509** covering the fin structures **501F1** and **501F2** and the STIs **508**, wherein the sidewalls of each of the fin structures **501F1** and **501F2** are partially exposed from corresponding one of the gate openings **502**. wherein Step **S53** includes Sub-steps **S531-S534**:

[0213] Referring to Sub-step **S531**: An inserting dielectric layer **511** is formed to surround the sidewalls of the fin structures **501F1** and **501F2**, and referring to Sub-step **S532**: An oxide deposition process is performed to form the capping dielectric layer **509** on the fin structures **501F1** and **501F2** and the inserting dielectric layer **511**. See FIGS. **5C(1)** to FIG. **5C(3)**, FIG. **5C(1)** is a top view illustrating the structure after the inserting dielectric layer **511** and the capping dielectric layer **509** are formed; FIG. **5C(2)** is a cross-sectional view taken along the cutting line **C5C1** as depicted in FIG. **5C(1)**; and FIG. **5C(3)** is a cross-sectional view taken along the cutting line **C5C2** as depicted in FIG. **5C(1)**.

[0214] In some embodiments of the present disclosure, the material constituting the dielectric layer **511** may be different from that constituting the capping dielectric layer **509**. In the present embodiment, the dielectric layer **511** is formed by a low-k dielectric material (such as, SiCOH) deposition process to covering the top surface of the remaining portion of the semiconductor substrate **501**. The deposited low-k dielectric material may be planarized by a chemical-mechanical polishing (CMP), and then etched backed using the patterned pad nitride layer **510B**, nitride spacers **507B** and the amorphous silicon spacers **507C** as an etching stop layer. Such that, the patterned pad nitride layer **510B**, nitride spacers **507B** and the amorphous silicon spacers **507C** can be exposed from the partially filled trenches **501T**.

[0215] Sub-step **S532**: the oxide deposition process for forming the capping dielectric layer **509** includes depositing SiO₂ to fulfill the trenches **501T** and is followed by a planarization process (such as, CMP). The bottom of the inserting dielectric layer **511** (SiCOH) is lower than the bottom of the remained STI regions **508**. Since the dielectric constant of the inserting dielectric layer **511** (SiCOH) is lower than that of the STI regions **508**, therefore, the coupling effect between two gate structures **504** and **506** (as shown below) could be improved.

[0216] Referring to Sub-step **S533**: A patterned process is performed to remove a portion of the capping dielectric layer **509** to define the gate opening **502**. In some embodiment, a patterned photoresist layer (not shown) is formed on the capping dielectric layer **509** to expose the portion of the capping dielectric layer **509** covering the fin structures **501F1** and **501F2**. Then, an etching process is performed to remove the exposed portion of the capping dielectric layer **509** to define the gate opening **502** in the capping dielectric layer **509**.

[0217] Referring to Sub-step **S534**: the amorphous silicon spacers **507C**, the nitride spacers **507B** and the oxide spacers **507A** are removed, so as to make each of the fin structures **501F1** and **501F2** partially exposed from the gate opening **502**. In the present embodiment, after the gate opening **502** is defined in the capping dielectric layer **509**, another etching process is performed to remove the amorphous silicon spacers **507C** not covered by the patterned photoresist layer (not shown) from the gate opening **502**.

[0218] Next, another process is performed remove the nitride spacers **507B** and the portion of the patterned pad nitride **510B** from the gate opening **502**. After the patterned photoresist layer PR is peeled, the oxide spacers **507A** and the portion of the patterned pad oxide layer **510A** exposed from the gate opening **502** are removed by another etching process, so as to expose the tops and

sidewalls of each fin structures **501F1** and **501F2**. See FIGS. **5D(1)** to **FIG. 5D(3)**, **FIG. 5D(1)** is a top view illustrating the structure after the fin structures **501F1** and **501F2** are partially exposed from the gate opening **502**; **FIG. 5D(2)** is a cross-sectional view taken along the cutting line **C5D1** as depicted in **FIG. 5D(1)**; and **FIG. 5D(3)** is a cross-sectional view taken along the cutting line **C5D2** as depicted in **FIG. 5D(1)**.

[0219] Referring to Steps **S54**: Gate structures **504** and **505** are formed respectively on the fin structures **501F1** and **501F2**. See FIGS. **5E(1)** to **5E(3)**. **FIG. 5E(1)** is a top view illustrating the structure after the gate structures **504** and **505** are formed; **FIG. 5E(2)** is a cross-sectional view taken along the cutting line **C5E1** as depicted in **FIG. 5E(1)**; and **FIG. 5E(3)** is a cross-sectional view taken along the cutting line **C5E2** as depicted in **FIG. 5E(1)**.

[0220] The Step **S54** for forming the gate structures **504** and **505** includes Sub-steps **S541-S542**: Referring to Sub-step **S541**: The gate dielectric layers **504O** and **505O** are formed respectively covering the tops and sidewalls of the fin structures **501F1** and **501F2**. In some embodiments of the present disclosure, the gate dielectric layers **504O** and **505O** are formed by an oxide deposition process. Then, referring to Sub-step **S542**: The gate electrodes **504S** and **505S** are formed respectively covering the gate dielectric layers **504O** and **505O**. In some embodiments of the present disclosure, the gate electrodes **504S** and **505S** are formed by polysilicon or metal. After the forming of the gate structures **504** and **505**, the capping dielectric layer **309** is then removed, and the source/drain regions could be formed as previously mentioned.

[0221] Compared with Embodiment II, in the present embodiment, between two gate structures **504** and **505**, the bottom of the inserting dielectric layer **511** (**SiCOH**) is lower than the bottom of the STIs **508**. Since the dielectric constant of the inserting dielectric layer **511** (**SiCOH**) is lower than that of the STI region **508**, therefore, the coupling effect between two gate structures **504** and **505** could be improved.

[0222] Those skilled in the art will readily observe that numerous modifications and alterations of the device and method may be made while retaining the teachings of the invention. Accordingly, the above disclosure should be construed as limited only by the metes and bounds of the appended claims.

Claims

1. A method for forming a metal-oxide-semiconductor (MOS) transistor structure, comprising: defining a first fin structure and a second fin structure adjacent to the first fin structure in a semiconductor substrate, wherein a shallow trench isolation (STI) region is between the first fin structure and the second fin structure; forming a first sacrificial spacer disposed along sidewalls of the first fin structure and forming a second sacrificial spacer disposed along sidewalls of the second fin structure, wherein a gap is between the first sacrificial spacer and the second sacrificial spacer; forming an inserting dielectric layer to fill the gap between the first sacrificial spacer and the second sacrificial spacer; removing the first sacrificial spacer and the second sacrificial spacer; and forming two gate structures over the first fin structure and the second fin structure respectively, wherein the two gate structures are separated by the inserting dielectric layer.
2. The method according to claim 1, wherein the first sacrificial spacer and the second sacrificial spacer comprise an epitaxial semiconductor material selectively grown based on the sidewalls of the first fin structure and the second fin structure.
3. The method according to claim 2, prior to forming the first sacrificial spacer and the second sacrificial spacer, further comprising: forming a capping dielectric layer covering the first fin structure and the second fin structure; and defining a gate opening in the capping dielectric layer to make the sidewalls of the first fin structure and the second fin structure partially exposed from the gate opening.
4. The method according to claim 3, further comprising: forming a fin spacer to surround the

sidewalls of the first fin structure and the second fin structure, prior to forming the capping dielectric layer; and performing at least one etching process to remove the fin spacer in the gate opening to make the sidewalls of the first fin structure and the second fin structure partially exposed, prior to forming the first sacrificial spacer and the second sacrificial spacer.

5. The method according to claim 3, wherein a material of the inserting dielectric layer is different from that of the capping dielectric layer.

6. The method according to claim 3, further comprising: deepening the gate opening to expose the semiconductor substrate, after the epitaxial semiconductor material is formed and prior to the gate opening is filled with the inserting dielectric layer.

7. The method according to claim 6, wherein a portion of the semiconductor substrate is removed during the process of deepening the gate opening.

8. The method according to claim 6, wherein a portion of the STI region is removed during deepening the gate opening, so as to remain another portion of the STI region beneath the epitaxial semiconductor material.

9. The method according to claim 8, wherein a bottom of the inserting dielectric layer is lower than a bottom of the another portion of the STI region.

10. The method according to claim 1, wherein a dielectric constant of the inserting dielectric layer is lower than that of SiO₂.

11. The method according to claim 1, wherein the first sacrificial spacer and the second sacrificial spacer comprises amorphous silicon covering the sidewalls of the first fin structure the second fin structure.

12. The method according to claim 11, further comprising: forming a fin spacer to surround the sidewalls of the first fin structure and the second fin structure, prior to forming the first sacrificial spacer and the second sacrificial spacer.

13. The method according to claim 11, further comprising: forming a capping dielectric layer covering the first fin structure, the second fin structure, the first sacrificial spacer, the second sacrificial spacer and the inserting dielectric layer; and defining a gate opening in the capping dielectric layer to make the sidewalls of the first fin structure and the second fin structure partially exposed from the gate opening.

14. The method according to claim 11, further comprising: removing a portion of the STI region not covered by the first sacrificial spacer and the second sacrificial spacer to expose a portion of the semiconductor substrate, prior to removing the sacrificial spacer.

15. The method according to claim 14, wherein a bottom of the inserting dielectric layer is lower than a bottom of another portion of the STI region beneath the first sacrificial spacer and the second sacrificial spacer.

16. A metal-oxide-semiconductor (MOS) transistor structure, comprising: a first active region and a second active region adjacent to the first active region in a semiconductor substrate, wherein a shallow trench isolation (STI) region is between the first active region and the second active region; an inserting dielectric layer disposed between the first active region and the second active region; a first trench surrounding or over the first active region, wherein the first trench is adjacent to one side of the inserting dielectric layer; a second trench surrounding or over the second active region, wherein the second trench is adjacent to another side of the inserting dielectric layer; a first gate structure over the first active region and within the first trench, wherein the first gate structure covers a first portion of the STI region; a second gate structure over the second active region and within the first trench, wherein the second gate structure covers a second portion of the STI region; a first source region and a first drain region electrically contacting to a first channel within the first active region; and a second source region and a second drain region electrically contacting to a second channel within the second active region; wherein a distance between the first gate structure and the second gate structure is decided by the inserting dielectric layer.

17. The MOS transistor structure according to claim 16, wherein a width of the inserting dielectric

layer between the active region and the second active region is not defined by a photolithographic process.

18. A metal-oxide-semiconductor (MOS) transistor structure, comprising: a first fin structure and a second fin structure adjacent to the first fin structure in a semiconductor substrate, wherein a shallow trench isolation (STI) region is between the first fin structure and the second fin structure; an inserting dielectric layer disposed between the first fin structure and the second fin structure; a first trench surrounding or over the first fin structure, wherein the first trench is adjacent to one side of the inserting dielectric layer; a second trench surrounding or over the second fin structure, wherein the second trench is adjacent to another side of the inserting dielectric layer; a first gate structure over the first fin structure and within the first trench, wherein the first gate structure covers a first portion of the STI region; and a second gate structure over the second fin structure and within the first trench, wherein the second gate structure covers a second portion of the STI region; wherein a bottom of the inserting dielectric layer is lower than that of the first portion of the STI region or the second portion of the STI region.

19. The MOS transistor structure according to claim 16, further comprising: a first source region and a first drain region electrically contacting to a first channel within the first fin structure; and a second source region and a second drain region electrically contacting to a second channel within the second fin structure.
