

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250282665

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

MAEHARA; Terutaka et al.

GLASS MANUFACTURING APPARATUS AND GLASS MANUFACTURING METHOD

Abstract

A glass manufacturing apparatus (1) includes a recuperator (60) configured to heat a heat medium through heat exchange with a combustion gas emitted from a glass melting furnace (10), a first reactor (71) configured to produce CH.sub.4 gas and H.sub.2O gas from CO.sub.2 gas and H.sub.2 gas by performing a methanation reaction, an water vapor controller (73) configured to adjust an H.sub.2O concentration in a product of the first reactor by removing at least a part of the H.sub.2O gas from the product of the first reactor, a second reactor (72) configured to produce CO gas and H.sub.2 gas from the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller by performing at least one of a dry reforming reaction and a steam reforming reaction through heat exchange with the heat medium heated by the recuperator, and a burner (20) configured to form a flame in the glass melting furnace by burning a oxidizing gas and a flammable gas containing the CO gas and the H.sub.2 gas produced by the second reactor.

Inventors: MAEHARA; Terutaka (Tokyo, JP), TANAKA; Toshiyuki (Tokyo, JP),
OKAMOTO; Mio (Tokyo, JP), SUZUKI; Yudai (Tokyo, JP)

Applicant: AGC Inc. (Tokyo, JP)

Family ID: 1000008667306

Assignee: AGC Inc. (Tokyo, JP)

Appl. No.: 19/217678

Filed: May 23, 2025

Foreign Application Priority Data

JP	2022-188270	Nov. 25, 2022
----	-------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: C03B5/237 (20060101); C03B5/235 (20060101)

U.S. Cl.:

CPC C03B5/237 (20130101); C03B5/2353 (20130101);

Background/Summary

TECHNICAL FIELD

[0001] The present disclosure relates to a glass manufacturing apparatus and a glass manufacturing method.

BACKGROUND ART

[0002] A glass manufacturing apparatus includes a burner that forms a flame inside a glass melting furnace. The burner burns a flammable gas and an oxidizing gas to form a flame. The flammable gas is, for example, natural gas. The natural gas contains CH₄ gas as the major component. The oxidizing gas is, for example, pure oxygen gas or air. The flame heats a glass raw material and molten glass obtained by melting the glass raw material.

[0003] Air may be used as the oxidizing gas as described above. In this case, because N₂ gas, which makes up the majority of the air, does not contribute to combustion, a large amount of air is used and a large amount of combustion gas is emitted from a glass melting furnace. The combustion gas is a gas that remains after a combustion reaction of the flammable gas and the oxidizing gas (including N₂ gas that does not contribute to a combustion reaction). A first regenerator and a second regenerator may be provided adjacent to the glass melting furnace so that heat is collected from a large amount of combustion gas that has been emitted.

[0004] The first regenerator and the second regenerator are used in combination with first and second burners. A glass manufacturing apparatus alternately and iteratively performs a process in which the first burner forms a flame inside the glass melting furnace and the second burner forms a flame inside the glass melting furnace.

[0005] The first regenerator collects heat from the combustion gas emitted from the glass melting furnace while the second burner forms a flame inside the glass melting furnace. The first regenerator releases the collected heat to heat at least one of the flammable gas and the oxidizing gas while the first burner forms a flame inside the glass melting furnace. The first burner burns at least one of the flammable gas and the oxidizing gas heated in the first regenerator to form a flame inside the glass melting furnace.

[0006] Likewise, the second regenerator collects heat from the combustion gas emitted from the glass melting furnace while the first burner forms a flame inside the glass melting furnace. The second regenerator releases the collected heat to heat at least one of the flammable gas and the oxidizing gas while the second burner forms a flame inside the glass melting furnace. The second burner burns at least one of the flammable gas and the oxidizing gas heated in the second regenerator to form a flame inside the glass melting furnace.

[0007] The first regenerator disclosed in Patent Document 1 releases heat while the first burner forms a flame inside the glass melting furnace, thereby performing an endothermic reaction. As an example of the endothermic reaction, a reaction for producing CO gas and H₂ gas from CH₄ gas, H₂O gas, and CO₂ gas is disclosed. The CO gas and the H₂ gas

produced in the first regenerator are supplied to the first burner as the flammable gas.

[0008] Moreover, pure oxygen gas may be used as the oxidizing gas as described above. In this case, the oxidizing gas does not contain N.sub.2 gas. Therefore, because an amount of combustion gas to be emitted is small and the regenerator is not required, a degree of freedom in the design of the glass melting furnace is increased. Moreover, N.sub.2 gas, which does not contribute to combustion, is not ineffectively heated and glass can be efficiently heated by combustion heat. Furthermore, the production of NO.sub.x gas can be suppressed.

[0009] A recuperator may be used instead of a regenerator as a means for collecting the heat of the combustion gas emitted from the glass melting furnace.

[0010] The recuperator of Patent Document 2 heats air through heat exchange with the combustion gas. Air transports heat from the recuperator to a reactor. The reactor heats natural gas through heat exchange with air heated in the recuperator to perform an endothermic reaction for producing CH.sub.4 gas from C.sub.mH.sub.n gas contained in the natural gas (m and n are integers of 2 or more).

[0011] Patent Document 3 discloses that when an H.sub.2O gas concentration in the furnace atmosphere of the glass melting furnace is excessively high, a moisture concentration contained in the molten glass is excessively high and the glass quality is low (for example, a defect occurs in a bottom surface of the float glass).

CITATION LIST

Patent Document

[0012] Patent Document 1: Japanese Patent No. 3705713

[0013] Patent Document 2: Japanese Patent No. 6980795

[0014] Patent Document 3: Japanese Patent No. 6144622

SUMMARY OF INVENTION

Technical Problem

[0015] Natural gas is commonly used as a flammable gas that is burned by a burner. The natural gas mainly contains CH.sub.4 gas. When the CH.sub.4 gas is burned, CO.sub.2 gas is produced and the CO.sub.2 gas is emitted. Therefore, a process in which H.sub.2 gas is used instead of the CH.sub.4 gas so that an amount of CO.sub.2 gas to be produced and an amount of CO.sub.2 gas to be emitted are reduced is conceived.

[0016] When the H.sub.2 gas is burned instead of the CH.sub.4 gas, the H.sub.2O gas is produced by a reaction between the H.sub.2 gas and O.sub.2 gas and the CO.sub.2 gas is not produced. However, the H.sub.2O gas concentration in the furnace atmosphere is high because CO.sub.2 gas is not produced. This is noticeable when pure oxygen gas is used as an oxidizing gas. When the pure oxygen gas is used, the H.sub.2O gas concentration in the furnace atmosphere can theoretically be 100% by volume.

[0017] In addition, the glass raw material may emit a gas during melting. For example, when the glass raw material contains a carbonate such as calcium carbonate or magnesium carbonate, the glass raw material releases the CO.sub.2 gas during melting.

[0018] Therefore, the H.sub.2O gas concentration in the furnace atmosphere is actually less than 100% by volume.

[0019] When the H.sub.2O gas concentration in the furnace atmosphere is excessively high, NaOH gas derived from Na contained in the molten glass is easily produced and furnace materials such as refractories are easily corroded. Alternatively, when the H.sub.2O gas concentration in the furnace atmosphere is excessively high, the moisture concentration in the molten glass may be excessively high and the glass quality may be low.

[0020] An aspect of the present disclosure provides a technique for reducing an H.sub.2O gas concentration in a furnace atmosphere of a glass melting furnace when H.sub.2 gas is used as a flammable gas.

Solution to Problem

[0021] According to an aspect of the present disclosure, there is provided a glass manufacturing apparatus including: a recuperator configured to heat a heat medium through heat exchange with a combustion gas emitted from a glass melting furnace; a first reactor configured to produce CH₄ gas and H₂O gas from CO₂ gas and H₂ gas by performing a methanation reaction; an water vapor controller configured to adjust an H₂O concentration in a product of the first reactor by removing at least a part of the H₂O gas from the product of the first reactor; a second reactor configured to produce CO gas and H₂ gas from the product of the first reactor with the H₂O concentration adjusted in the water vapor controller by performing at least one of a dry reforming reaction and a steam reforming reaction through heat exchange with the heat medium heated by the recuperator; and a burner configured to form a flame in the glass melting furnace by burning a oxidizing gas and a flammable gas containing the CO gas and the H₂ gas produced by the second reactor.

Advantageous Effects of Invention

[0022] According to the aspect of the present disclosure, when the H₂ gas is used as the flammable gas, a transformation is performed to produce at least the CO gas from the H₂ gas and the CO₂ gas, and the flammable gas containing the produced CO gas and the oxidizing gas are burned by the burner. Thereby, the H₂O gas concentration in the combustion gas can be reduced and the H₂O gas concentration in a furnace atmosphere of the glass melting furnace can be reduced. Moreover, by removing at least the part of the H₂O gas after the methanation reaction and before at least one of the dry reforming reaction and the steam reforming reaction, the H₂O gas concentration in the furnace atmosphere of the glass melting furnace can be further reduced.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0023] FIG. 1 A diagram showing a glass manufacturing apparatus according to a reference embodiment.

[0024] FIG. 2 A diagram showing an example (x=0.5) of a reaction in which an overall reaction is represented by Eq. (1).

[0025] FIG. 3 A diagram showing Examples 1 to 14 of combinations of a flammable gas, a oxidizing gas, an H₂O gas concentration in a combustion gas, and an H₂O gas concentration in a furnace atmosphere.

[0026] FIG. 4 A diagram showing a first embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0027] FIG. 5 A diagram showing a second embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0028] FIG. 6 A diagram showing a third embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0029] FIG. 7 A diagram showing a fourth embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0030] FIG. 8 A diagram showing a fifth embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0031] FIG. 9 A diagram showing a sixth embodiment of a glass manufacturing apparatus including a recuperator and a reactor.

[0032] FIG. 10 A diagram showing a first embodiment of a glass manufacturing apparatus including a first regenerator and a second regenerator.

[0033] FIG. 11 A diagram showing a second embodiment of a glass manufacturing apparatus including a first regenerator and a second regenerator.

[0034] FIG. **12** A diagram showing a third embodiment of a glass manufacturing apparatus including a first regenerator and a second regenerator.

[0035] FIG. **13** A diagram showing a fourth embodiment of a glass manufacturing apparatus including a first regenerator and a second regenerator.

[0036] FIG. **14** A diagram showing an example of a condition for suppressing a byproduct of C in the second reactor.

[0037] FIG. **15** A diagram showing an example of an equilibrium composition when a gas mixture of an initial composition shown at point P1 ($a=0.5$ and $b=0.5$) in FIG. **14** is heated.

[0038] FIG. **16** A diagram showing an example of a relationship of a molar ratio x , a CH_{sub.4} selectivity, and a temperature in the first reactor.

DESCRIPTION OF EMBODIMENTS

[0039] Hereinafter, embodiments of the present disclosure will be described with reference to the drawings. In each drawing, the same or corresponding constituent elements are denoted by the same reference signs and the description thereof may be omitted. In the description, “to (～)” indicating a numerical range means that numerical values written before and after “to (～)” include a lower limit value and an upper limit value.

[0040] A glass manufacturing apparatus **1** according to a reference embodiment will be described with reference to FIG. **1**. The glass manufacturing apparatus **1** includes a glass melting furnace **10**. The glass melting furnace **10** houses a glass raw material and molten glass obtained by melting the glass raw material. After the molten glass is removed from the glass melting furnace **10**, the molten glass is molded into a desired shape and slowly cooled. Thereby, a glass product is obtained.

[0041] The glass raw material is prepared by mixing several types of materials. The glass raw material may contain a fining agent. The glass raw material may include glass cullet to recycle glass. The glass raw material may be a powdered raw material or a granulated raw material obtained by granulating the powdered raw material. The glass raw material is decided in accordance with a composition of the glass product.

[0042] The glass melting furnace **10** includes refractories. The refractories include, for example, zirconia-based fused cast refractories, alumina-based fused cast refractories, alumina-zirconia-based fused cast refractories, Al—Zr—Si (AZS)-based fused cast refractories, dense bonded refractories, and the like. The glass melting furnace **10** may include a plurality of types of refractory refractories.

[0043] The glass manufacturing apparatus **1** includes a burner **20**. The burner **20** forms a flame inside the glass melting furnace **10**. The flame heats the glass raw material and the molten glass. The glass raw material is input from above with respect to a surface level of the molten glass and forms a layer on at least a part of the surface level. The glass raw material is gradually fused into the molten glass. Although only one of the burners **20** is shown in FIG. **1**, the number of burners **20** is typically two or more.

[0044] In addition, the glass manufacturing apparatus **1** may use a plurality of electrodes (not shown) as a heat source. The plurality of electrodes perform a current-carrying process on the molten glass by applying an alternating current (AC) voltage to the molten glass. In this case, the molten glass is heated. The glass manufacturing apparatus **1** may use an electric heater (not shown) as a heat source. The electric heater itself produces heat. It is only necessary for the glass manufacturing apparatus **1** to include at least the burner **20** as a heat source.

[0045] The burner **20** forms a flame by burning a flammable gas and an oxidizing gas. In the present reference embodiment, at least a part of the flammable gas is H_{sub.2} gas (more specifically, a gas obtained by transforming the H_{sub.2} gas as will be described below). The use of the H_{sub.2} gas can reduce the amount of CO_{sub.2} gas that is produced and the amount of CO_{sub.2} gas to be emitted compared with the use of CH_{sub.4} gas.

[0046] In addition, it is only necessary for the H_{sub.2} gas to be used as at least a part of the flammable gas and it is only necessary to use the natural gas in combination therewith. Because the

natural gas contains CH₄ gas as a main component, an amount of natural gas to be used is more preferably smaller. The amount of natural gas to be used is preferably 0% to 50% by volume, more preferably 0% to 25% by volume, and even more preferably 0% by volume, from the viewpoint of reducing the amount of CO₂ gas to be produced.

[0047] When the H₂ gas is burned instead of the CH₄ gas, the H₂O gas is produced by a reaction between the H₂ gas and O₂ gas, and the CO₂ gas is not produced. However, an H₂O gas concentration in the furnace atmosphere is high because the CO₂ gas is not produced. This is noticeable when pure oxygen gas is used as the oxidizing gas. When the pure oxygen gas is used, the H₂O gas concentration in the furnace atmosphere can theoretically be 100% by volume.

[0048] In addition, the glass raw material may release a gas during melting. For example, if the glass raw material contains a carbonate such as calcium carbonate or magnesium carbonate, the glass raw material releases CO₂ gas during melting. Therefore, the H₂O gas concentration in the furnace atmosphere is actually less than 100% by volume.

[0049] If the H₂O gas concentration in the furnace atmosphere is excessively high, NaOH gas derived from Na contained in the molten glass is easily produced and furnace materials such as refractories are easily corroded. Alternatively, when the H₂O gas concentration in the furnace atmosphere is excessively high, a moisture concentration in the molten glass may be excessively high and the glass quality may be low.


[0050] If air is used instead of pure oxygen gas as the oxidizing gas, the H₂O gas concentration in the furnace atmosphere can be reduced. In this case, because the N₂ gas, which makes up the majority of the air, does not contribute to combustion, a large amount of air is used and a large amount of combustion gas is emitted from the glass melting furnace. The combustion gas is a gas that remains after a combustion reaction of the flammable gas and the oxidizing gas (including the N₂ gas that does not contribute to combustion). To collect the heat of the large amount of combustion gas that has been emitted, a regenerator is provided adjacent to the glass melting furnace **10**.

[0051] On the other hand, if the pure oxygen gas is used as the oxidizing gas, the oxidizing gas does not contain N₂ gas. Therefore, because an amount of combustion gas to be emitted is small and the regenerator is not required, the degree of freedom in the design of the glass melting furnace **10** is increased. Moreover, the N₂ gas, which does not contribute to combustion, is not ineffectively heated and glass can be efficiently heated by combustion heat. Furthermore, the production of NO_x gas can be suppressed.

[0052] However, if the pure oxygen gas is used as the oxidizing gas, an H₂O gas concentration in the furnace atmosphere is higher than when air is used. When oxygen-enriched air is used instead of pure oxygen gas as the oxidizing gas, the H₂O gas concentration is higher than when air is used. The oxygen-enriched air is a gas mixture of pure oxygen gas and air and is a gas having a higher oxygen gas concentration than air.

[0053] The glass manufacturing apparatus **1** of the present reference embodiment includes a gas transformer **30** that transforms the H₂ gas to reduce the H₂O gas concentration in the furnace atmosphere. One or more gas transformers **30** (one gas transformer **30** in FIG. **1**) are provided. The gas transformer **30** produces at least the CO gas and the H₂O gas from the CO₂ gas and the H₂ gas according to a reaction in which an overall reaction is represented by the following Eq. (1) or (2). The CO₂ gas and the H₂ gas are reactants and the CO gas and the H₂O gas are products. The product may further include at least one of the H₂ gas and the CO₂ gas.

[Chem. 1]



[Chem. 2]



[0054] In Eqs. (1) and (2), x denotes a molar ratio of the CO.sub.2 gas to the H.sub.2 gas supplied to the gas transformer **30**. The molar ratio x is greater than 0.00. In general, the molar ratio is consistent with a volume ratio.


[0055] In addition, it is only necessary for the gas transformer **30** to perform a reaction in which the overall reaction is represented by Eq. (1) or Eq. (2) and this reaction may be simultaneously performed with a reaction different therefrom. Thus, it is only necessary to supply the CO.sub.2 gas and the H.sub.2 gas as the reactants to the gas transformer **30**, and other gases may be further supplied.

[0056] In FIG. 2, an example ($x=0.5$) of a reaction in which the overall reaction is given by Eq. (1) is shown. In FIG. 2, ΔH is a variation in enthalpy (KJ/mol). The enthalpy is also referred to as heat content. As can be seen from FIG. 2, the reaction in which the overall reaction is represented by Eq. (1) or (2) is an endothermic reaction. The product of the endothermic reaction (the CO gas) potentially contains more heat than the reactant of the endothermic reaction (the H.sub.2 gas).


[0057] Reactions in which the overall reaction is represented by Eq. (1) or (2) include, for example, at least one of (A) a reverse shift (a reverse water gas shift: RWGS) reaction, (B) a combination of a methanation reaction and a dry reforming (DRM) reaction, and (C) a combination of a methanation reaction and a steam reforming (STR) reaction.

[0058] Compared to the above-described (B) and (C), the above-described (A) can reduce the number of reactions used and simplify the apparatus configuration. On the other hand, the above-described (B) and (C) can lower the reaction temperature compared to the above-described (A). Incidentally, the reverse shift reaction is represented by the following Eq. (3). The methanation reaction is represented by the following Eq. (4). The DRM reaction is represented by the following Eq. (5). In addition, the STR reaction is represented by the following Eq. (6).

[Chem. 3]



[Chem. 4]



[Chem. 5]



[Chem. 6]



[0059] From Eq. (3), it can be seen that the reverse shift reaction is an endothermic reaction. From Eq. (4), it can be seen that the methanation reaction is an exothermic reaction. From Eq. (5), it can be seen that the DRM reaction is the endothermic reaction. From Eq. (6), it can be seen that the STR reaction is the endothermic reaction.

[0060] The product of the endothermic reaction (the CO gas) potentially contains more heat than the reactant of the endothermic reaction (the H.sub.2 gas or the CH.sub.4 gas). Therefore, the combustion of the product of the endothermic reaction (the CO gas) yields more combustion heat


than the combustion of the reactant of the endothermic reaction (the H.sub.2 gas or the CH.sub.4 gas).

[0061] The gas transformer **30** supplies a product such as the CO gas to the burner **20**. The gas to be supplied includes, for example, the CO gas and the H.sub.2O gas (see Eqs. (1) and (2)). The gas to be supplied may further include at least one of the H.sub.2 gas and the CO.sub.2 gas.


[0062] The burner **20** forms a flame inside the glass melting furnace **10** by burning a flammable gas containing the CO gas produced by the gas transformer **30** and an oxidizing gas. The combustion of the CO gas improves the heat of combustion per mole more than the combustion of the H.sub.2 gas.

[0063] The combustion reaction of the CO gas is represented by the following Eq. (7) and the combustion reaction of the H.sub.2 gas is represented by the following Eq. (8). Here, a lower heating value is used for the heat of combustion of the H.sub.2 gas.

[Chem. 7]




[Chem. 8]




[0064] From Eqs. (7) and (8), it can be seen that combustion of the CO gas can improve the heat of combustion per mole more than the combustion of the H.sub.2 gas.

[0065] The combustion reaction of the flammable gas and the oxidizing gas by the burner **20** is represented by, for example, the following Eq. (9) or (10).

[Chem. 9]



[Chem. 10]



[0066] Eq. (9) represents the combustion reaction of the product obtained in Eq. (1). On the other hand, Eq. (10) shows the combustion reaction of the product obtained in Eq. (2). In Eqs. (9) and (10), x denotes a molar ratio of the CO.sub.2 gas to the H.sub.2 gas supplied to the gas transformer **30**. The molar ratio x is greater than 0.00.

[0067] In addition, the combustion reaction of the flammable gas and the oxidizing gas may include at least the combustion reaction represented by Eqs. (9) and (10) and may further include another combustion reaction.

[0068] As described above, the burner **20** burns the flammable gas containing the CO gas produced by the gas transformer **30** and the oxidizing gas. Therefore, the combustion gas includes the CO.sub.2 gas as well as the H.sub.2O gas. This is also obvious from Eq. (9) and Eq. (10). The H.sub.2O gas can be diluted with the CO.sub.2 gas and the H.sub.2O gas concentration in the furnace atmosphere can be reduced.

[0069] Examples 1 to 14 of combinations of the flammable gas, the oxidizing gas, the H.sub.2O gas concentration in the combustion gas, and the H.sub.2O gas concentration in the furnace atmosphere are shown in FIG. 3. The furnace atmosphere includes a gas released by the glass raw material when the glass raw material is fused, in addition to the combustion gas. Therefore, the H.sub.2O gas concentration in the furnace atmosphere is lower than the H.sub.2O gas concentration in the combustion gas. The H.sub.2O gas concentration in the combustion gas shown in FIG. 3 is a numerical value of a case where the gas transformer **30** does not have the water vapor controller **73** to be described below. When the gas transformer **30** has the water vapor controller **73**, the H.sub.2O gas concentration in the combustion gas is less than the numerical value shown in FIG. 3.

[0070] As shown in FIG. 3, if the H.sub.2 gas is used instead of the CH.sub.4 gas as the flammable gas, the H.sub.2O gas concentration in the furnace atmosphere is high because the CO.sub.2 gas is

not produced. This is noticeable when pure oxygen gas is used as the oxidizing gas.

[0071] In addition, the H.sub.2O gas concentration in the furnace atmosphere depends on a type of glass raw material, but is mainly determined in accordance with a type of flammable gas and a type of oxidizing gas. Therefore, in the present reference embodiment, the H.sub.2O gas concentration in the combustion gas is adopted as a parameter to be managed.

[0072] The H.sub.2O gas concentration in the combustion gas is preferably 67% or less by volume. Molten glass has been conventionally manufactured by burning the CH₄ gas and the O₂ gas (pure oxygen gas). It has been confirmed that if the H.sub.2O gas concentration in the combustion gas is 67% or less by volume, there is no problem with the quality of the glass product or corrosion of the furnace material.

[0073] Preferably, the molar ratio x is 0.50 or more so that the H.sub.2O gas concentration in the combustion gas is 67% or less by volume (see FIG. 3). The H.sub.2O gas concentration in the combustion gas is more preferably 65% or less by volume. More preferably, the molar ratio x is 0.55 or more so that the H.sub.2O gas concentration in the combustion gas is 65% or less by volume (see FIG. 3).

[0074] Although a lower limit of the H.sub.2O gas concentration in the combustion gas is not particularly limited, the concentration is preferably 20% or more by volume from the viewpoint of feasibility. Preferably, the molar ratio x is 4.00 or less so that the H.sub.2O gas concentration in the combustion gas is 20% or more by volume (see FIG. 3).

[0075] More preferably, the molar ratio x is less than or equal to 1.00. If the molar ratio x is 1.00 or less, the combustion reaction is represented by Eq. (9). On the other hand, when the molar ratio x exceeds 1.00, the combustion reaction is represented by Eq. (10). As can be seen from Eq. (10), there is CO₂ gas of $(x-1)$ moles which does not contribute to combustion when the molar ratio x exceeds 1.00. This CO₂ gas not only does not produce combustion heat but also consumes combustion heat ineffectively. If the molar ratio x is 1.00 or less, CO₂ gas of $(x-1)$ moles which does not contribute to combustion will not be ineffectively heated and the glass will be heated efficiently with combustion heat.

[0076] Although a dedicated supply source such as a gas cylinder (not shown) may be used to supply the CO₂ gas to the gas transformer **30**, a circulation line **50** is used in the present reference embodiment. The circulation line **50** supplies at least a part of the CO₂ gas contained in the combustion gas from the glass melting furnace **10** to the gas transformer **30**. At least a part of the CO₂ gas emitted from the glass melting furnace **10** can be used as a reactant in the overall reaction. The CO₂ gas can be circulated and the amount of CO₂ gas to be emitted can be reduced.

[0077] A first dehydration unit **51** may be provided along the circulation line **50**. The first dehydration unit **51** separates the H.sub.2O gas and the CO₂ gas from each other by removing the H.sub.2O gas from the combustion gas. At least a part of the separated CO₂ gas can be used as a reactant in the overall reaction. The H.sub.2O gas supply to the gas transformer **30** can be limited, and the H.sub.2O gas concentration in the furnace atmosphere of the glass melting furnace **10** can be reduced. The first dehydration unit **51** may remove at least a part of the H.sub.2O gas, but substantially all of the H.sub.2O gas is removed in the present reference embodiment.

[0078] The glass manufacturing apparatus **1** preferably collects heat from the combustion gas burned by the burner **20** and uses the collected heat to perform the reaction in which the overall reaction is represented by Eq. (1) or (2). By collecting heat from the burned combustion gas, the waste of energy can be reduced. As a heat collection means, a recuperator or a regenerator to be described below is used. Hereinafter, the heat collection means and the like will be described.

[0079] A first embodiment of the glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. 4. The glass manufacturing apparatus **1** includes a glass melting furnace **10**, a burner **20**, the recuperator **60**, a first reactor **71**, and a second reactor **72**. The gas transformer **30** includes the first reactor **71**, the second reactor **72**, and the like (including an

water vapor controller **73** and an additive line **75** to be described below). The first reactor **71** performs the methanation reaction and the second reactor **72** performs at least one of the DRM and STR reactions. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **1** will be mainly described.

[0080] The recuperator **60** heats a heat medium through heat exchange with a combustion gas emitted from the glass melting furnace **10**. Although the heat medium may be a gas or a liquid, the heat medium is preferably a gas from the viewpoint of preventing boiling because the temperature of the combustion gas is high. The heat medium is preferably air. The recuperator **60** transfers heat between the combustion gases and the heat medium (e.g., air) without mixing them. The recuperator **60** is provided outside the glass melting furnace **10** in FIG. **4**, but may be provided inside the glass melting furnace **10**. One or more recuperators **60** (one recuperator **60** in FIG. **4**) are provided. The recuperator **60** is thermally connected to the second reactor **72** via a first heat transport line **80**. The first heat transport line **80** transports the heat medium from the recuperator **60** to the second reactor **72**.

[0081] The first reactor **71** produces CH_4 and H_2O gases from CO_2 and H_2 gases by performing a methanation reaction. The CO_2 and H_2 gases are reactants and the CH_4 and H_2O gases are products (see Eq. (4)). The methanation reaction is sufficiently performed even at a low temperature of 400°C . or lower.

[0082] The second reactor **72** produces CO gas from the product of the first reactor **71** by performing at least one of the DRM and STR reactions through heat exchange with a heat medium heated in the recuperator **60**. When both the DRM and STR reactions occur, the CH_4 and H_2O gases and the CO_2 gas are reactants and the CO and H_2 gases are products (see Eqs. (5) and (6)). The product may include at least one of gases such as the H_2O gas, the CO_2 gas, and the CH_4 gas other than the CO gas and the H_2 gas. The second reactor **72** does not mix the reactant and product of the second reactor **72** with a heat medium (e.g., air) and transfers heat therebetween.

[0083] Because the DRM reaction and the STR reaction are endothermic reactions, heat can be efficiently collected from the heat medium and heat collected from the combustion gas can be used efficiently. The product of the endothermic reaction (the CO gas) also potentially contains more heat than the reactant of the endothermic reaction (the H_2 gas). Therefore, the combustion of the CO gas can improve the heat of combustion per mole more than the combustion of the H_2 gas (see Eqs. (7) and (8)).

[0084] It is only necessary for the reaction occurring in the second reactor **72** to be an endothermic reaction as a whole. The reaction occurring in the second reactor **72** may include a reaction other than the DRM reaction and the STR reaction. Therefore, in the second reactor **72**, the reactant and product are not particularly limited. The product produced in the second reactor **72** (i.e., the flammable gas) is supplied to the burner **20** via the first supply line **21**. On the other hand, the oxidizing gas is supplied to the burner **20** via the second supply line **22**.

[0085] The glass manufacturing apparatus **1** includes an water vapor controller **73**. The water vapor controller **73** is provided along a connection line **74** connecting the first reactor **71** and the second reactor **72**. The water vapor controller **73** adjusts an H_2O concentration in the product of the first reactor **71** by removing at least a part of the H_2O gas from the product of the first reactor **71**. The water vapor controller **73** is removed, for example, by cooling and liquefying the H_2O gas. The second reactor **72** produces the CO gas from the product of the first reactor **71** in which the H_2O concentration is adjusted in the water vapor controller **73**.

[0086] In the present embodiment, the water vapor controller **73** removes at least a part of the H_2O gas from the product of the first reactor **71** and delivers the product of the first reactor **71** to the second reactor **72**. The H_2O concentration in the product of the second reactor **72** can be reduced and the H_2O concentration in the furnace atmosphere of the glass melting furnace **10** can be reduced.

[0087] A process of removing at least a part of the H.sub.2O gas from the product of the first reactor 71 and delivering the product of the first reactor 71 to the second reactor 72 is also effective in performing the overall reaction represented by Eq. (1) or (2). This is evident from the fact that H.sub.2O does not appear as the substance (reactant) on the left side of the general reaction equation, but is present as the substance (product) on the right side of the general reaction equation. By performing the above-described overall reaction and the endothermic reaction, the heat collection rate can be improved.

[0088] Preferably, the amount of H.sub.2O gas removed in the water vapor controller 73 is set so that C is not produced as a byproduct in the second reactor 72 (or so that soot is not deposited). The second reactor 72 performs at least one of the DRM reaction (see Eq. (5)) and the STR reaction (see Eq. (6)) as described above to produce the CO and H.sub.2 gases from at least one of the H.sub.2O and CO.sub.2 gases and the CH.sub.4 gas.

[0089] As can be seen from Eqs. (5) and (6), if the total number of moles of the H.sub.2O and CO.sub.2 gases is less than the number of moles of the CH.sub.4 gas, the CH.sub.4 gas remains. If the CH.sub.4 gas remains, because the reaction temperature in the second reactor 72 is 700° C. or higher, C will be produced as a byproduct according to pyrolysis of the CH.sub.4 gas. Thus, it is preferable to set the amount of H.sub.2O gas removal in the water vapor controller 73 so that soot is not deposited.

[0090] Next, the amount of H.sub.2O gas removed in the water vapor controller 73 will be described with reference to FIGS. 14 and 15. In FIGS. 14 and 15, a denotes a molar ratio (CO.sub.2/CH.sub.4) of the CO.sub.2 gas supplied to the second reactor 72 to the CH.sub.4 gas supplied to the second reactor 72 and b denotes a molar ratio (H.sub.2O/CH.sub.4) of the H.sub.2O gas supplied to the second reactor 72 to the CH.sub.4 gas supplied to the second reactor 72.

[0091] In order to prevent the byproduct of C in the second reactor 72, the water vapor controller 73 preferably removes only a part of the H.sub.2O gas from the product of the first reactor 71 so that the following Inequality (a1) is valid when a reaction temperature in the second reactor 72 is 900° C. or higher (preferably 1600° C. or lower), the following Inequality (a2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (a3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C.

$$[00003] \quad b \geq -a + 1 \quad (a1) \quad b \geq -0.68a + 1.01 \quad (a2) \quad b \geq -0.1143a^2 + 0.0286a + 1.3029 \quad (a3)$$

[0092] Here, the condition for preventing the byproduction of C in the second reactor 72 was obtained by calculating the equilibrium composition at atmospheric pressure at each temperature with a gas mixture in which CH.sub.4 gas of 1 mole, CO.sub.2 gas of a moles, and H.sub.2O gas of b moles are mixed as the initial composition. The equilibrium composition was calculated using the thermodynamic equilibrium calculation software (a software name of FactSage developed by GTT-Technologies).

[0093] In FIG. 15, an example of an equilibrium composition when a gas mixture of an initial composition shown at point P1 (a=0.5 and b=0.5) in FIG. 14 is heated is shown. As can be seen from FIG. 15, when the initial composition is (a=0.5 and b=0.5), the byproduct of C can be prevented if the temperature is 900° C. or higher. As can be seen from FIG. 15, if a and b are constant, the byproduct of C is more easily suppressed when the temperature is higher.

[0094] The inventors of the present invention have derived the above Inequalities (a1), (a2), and (a3) by calculating the minimum temperature required to prevent the byproduct of C using a and b as variables. In addition, when Inequality (a1) is valid, it indicates that the sum of a and b is 1 or more and indicates that the total number of moles of the H.sub.2O and CO.sub.2 gases is greater than or equal to the number of moles of the CH.sub.4 gas. When the above Inequality (a1) is not valid, the total number of moles of the H.sub.2O gas and the CO.sub.2 gas is less than the number of moles of the CH.sub.4 gas, and the excess of the CH.sub.4 gas results in the byproduct of C even when the reaction temperature is high.

[0095] More preferably, the water vapor controller **73** removes only a part of the H.sub.2O gas from the product of the first reactor **71** so that the following Inequality (a4) is valid in addition to any one of the above Inequalities (a1), (a2), and (a3).

[00004] $b \geq 2a$ (a4)

[0096] If the above Inequality (a4) is valid, an H.sub.2O gas concentration in the combustion gas of the burner **20** is 67% or less by volume. It has been confirmed that if the H.sub.2O gas concentration in the combustion gas is 67% or less by volume, there is no problem with the quality of the glass product or corrosion of the furnace material.

[0097] Moreover, more preferably, the water vapor controller **73** removes only a part of the H.sub.2O gas from the product of the first reactor **71** so that the following Inequality (a5) is valid in addition to any one of the above Inequalities (a1), (a2), and (a3).

[00005] $b \geq -a + 3$ (a5)

[0098] If the above Inequality (a5) is valid, a coking reaction in the surface of the metal catalyst can be suppressed when the second reactor **72** has the metal catalyst. The coking reaction is a reaction in which soot is deposited in a kinetically favorable side reaction, even under equilibrium conditions in which soot is not deposited. If soot covers the surface of the metal catalyst, the activity of the metal catalyst is reduced.

[0099] In addition, when the second reactor **72** does not have a metal catalyst, the above Inequality (a5) may or may not be valid. When the second reactor **72** does not have a metal catalyst, the following Inequality (a6) may be valid instead of the above Inequality (a5).

[00006] $b < -a + 3$. (a6)

[0100] If the above Inequality (a6) is valid, the amount of H.sub.2O gas removal in the water vapor controller **73** is large and the H.sub.2O gas concentration in the combustion gas is low.

[0101] The glass manufacturing apparatus **1** preferably includes an additive line **75**. The additive line **75** supplies at least a part of the CO.sub.2 gas for use in the DRM reaction to the second reactor **72** without passing through the first reactor **71**. Thereby, it is possible to reduce a molar ratio x in the first reactor **71** and suppress the deposition of soot in the first reactor **71**.

[0102] Next, an example of a relationship of the molar ratio x, the CH.sub.4 selectivity, and the temperature in the first reactor **71** will be described with reference to FIG. **16**. The molar ratio x is a molar ratio of the CO.sub.2 gas to the H.sub.2 gas as described above. The CH.sub.4 selectivity is a ratio of an amount of CH.sub.4 gas production to a total amount of product production in a methanation reaction (a reaction in which the CH.sub.4 gas and the H.sub.2O gas are produced from the CO.sub.2 gas and the H.sub.2 gas).

[0103] As shown in FIG. **16**, the CH.sub.4 selectivity is low if the temperature exceeds 500° C. When the temperature exceeds 500° C., the CH.sub.4 gas is expected to decompose. Accordingly, the temperature of the first reactor **71** is preferably 500° C. or lower, and more preferably 400° C. or lower. The methanation reaction is sufficiently performed even at a temperature of 400° C. or lower.

[0104] Moreover, as shown in FIG. **16**, when the molar ratio x is greater than 0.25, the CH.sub.4 selectivity is low. It is considered that if the molar ratio x exceeds 0.25, carbon is precipitated (or soot is deposited). Accordingly, it is preferable to have a molar ratio x of 0.25 or less in at least the first reactor **71** so that the deposition of soot in the first reactor **71** is suppressed.

[0105] In addition, the molar ratio x in the gas transformer **30**, which includes the first reactor **71**, the second reactor **72**, and the like, may exceed 0.25. It is only necessary for the molar ratio x in the first reactor **71** to be 0.25 or less.

[0106] CO.sub.2 gas is used in both the methanation reaction and the DRM reaction. Thus, although it is necessary to supply the CO.sub.2 gas to the first reactor **71**, it is not necessary to supply the CO.sub.2 gas for use in both the first reactor **71** and the second reactor **72** to the first reactor **71**.

[0107] The additive line 75 supplies at least a part of the CO.sub.2 gas for use in the second reactor 72 to the second reactor 72 without passing through the first reactor 71 so that the deposition of soot in the first reactor 71 is suppressed as described above. Thereby, it is possible to reduce the molar ratio x in the first reactor 71 and suppress the deposition of soot in the first reactor 71.

[0108] The additive line 75 branches from the circulation line 50, which will be discussed below, for example, to bypass the first reactor 71 and join the connection line 74. The additive line 75 may bypass not only the first reactor 71 but also the water vapor controller 73. Cooling of the CO.sub.2 gas can be suppressed by the water vapor controller 73. A flow rate controller 76 may be provided along the additive line 75.

[0109] Although the additive line 75 joins a connection line 74, the additive line 75 may be connected to the second reactor 72 without joining the connection line 74. In the former case, the product of the first reactor 71 and the CO.sub.2 gas are premixed and supplied to the second reactor 72. In the latter case, the product of the first reactor 71 and the CO.sub.2 gas are separately supplied to the second reactor 72.

[0110] The glass manufacturing apparatus 1 preferably includes a circulation line 50. The circulation line 50 supplies at least a part of the CO.sub.2 gas contained in the combustion gas burned by the burner 20 from the glass melting furnace 10 to the first reactor 71. At least a part of the CO.sub.2 gas emitted from the glass melting furnace 10 can be used as a reactant in the methanation reaction. The CO.sub.2 gas can be circulated and an amount of CO.sub.2 gas to be emitted can be reduced. At least a part of the CO.sub.2 gas emitted from the glass melting furnace 10 can also be used as a reactant in the DRM or STR reaction.

[0111] The glass manufacturing apparatus 1 may include a first dehydration unit 51 along the circulation line 50. The first dehydration unit 51 separates the H.sub.2O gas from the CO.sub.2 gas by removing the H.sub.2O gas from the combustion gas. It is possible to restrict the circulation of the H.sub.2O gas while permitting the circulation of CO.sub.2 gas. The H.sub.2O gas not only does not produce heat of combustion but also ineffectively consumes heat of combustion. If the circulation of H.sub.2O gas can be restricted, the non-flammable H.sub.2O gas can be avoided, and the heat of combustion can be used to heat glass efficiently. If the circulation of H.sub.2O gas can be restricted, the concentration of H.sub.2O gas in the furnace atmosphere can be reduced.

[0112] Although it is only necessary for the first dehydration unit 51 to remove at least a part of the H.sub.2O gas, substantially all of the H.sub.2O gas is removed in the present embodiment. When only a part of the H.sub.2O gas is removed from the first dehydration unit 51 or when there is no first dehydration unit 51 as described below, the gas containing the H.sub.2O gas is supplied to the first reactor 71.

[0113] More preferably, a desulfurization unit 52 is provided along the circulation line 50. The desulfurization unit 52 removes a sulfur-containing gas from the combustion gas. The sulfur contained in the sulfur-containing gas is derived from a glass raw material, for example, a fining agent. The supply of the sulfur-containing gas to the first reactor 71 can be restricted by providing the desulfurization unit 52 along the circulation line 50. Thereby, the first reactor 71 can be maintained in a clean state.

[0114] Because the second reactor 72 uses a heat medium to collect heat from the combustion gas unlike a regenerator to be described below, it is possible to restrict a process in which the combustion gas flows into the second reactor 72 as it is and it is possible to maintain the second reactor 72 in a clean state. Therefore, when the second reactor 72 has a metal catalyst, the deterioration of the metal catalyst can be suppressed.

[0115] The second reactor 72 may have a metal catalyst. The metal catalyst promotes at least one of the DRM reaction and the STR reaction. The metal catalyst can increase a reaction rate of at least one of the DRM reaction and the STR reaction and cause the reaction to equilibrate in a short time. The metal catalyst may also reduce a volume of the second reactor 72 by increasing the reaction rate. As a metal catalyst, copper (Cu), nickel (Ni), or the like is used. If the reaction rate is

sufficiently fast, the metal catalyst may be eliminated.

[0116] A second embodiment of a glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. 5. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. 4 will be mainly described. As shown in FIG. 5, the glass manufacturing apparatus **1** may not include the first dehydration unit **51** (see FIG. 4). An water vapor controller **73** may also serve as the first dehydration unit **51**.

[0117] A third embodiment of a glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. 6. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. 4 will be mainly described. As shown in FIG. 6, the water vapor controller **73** may include a dehydration unit **73a** in which a part of H.sub.2O gas is removed by cooling and liquefying and a bypass line **73b** along which the remaining part of the H.sub.2O gas is delivered from a first reactor **71** to a second reactor **72**.

[0118] According to the present embodiment, all unnecessary H.sub.2O gas can be removed in the dehydration unit **73a** while the H.sub.2O gas for use in the STR reaction remains. Moreover, the H.sub.2O gas for use in the STR reaction can also be delivered from the first reactor **71** to the second reactor **72** without cooling in the dehydration unit **73a**. The bypass line **73b** bypasses the dehydration unit **73a**. A flow rate controller **73c** may be provided along the bypass line **73b**.

[0119] A fourth embodiment of a glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. 7. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. 4 will be mainly described. As shown in FIG. 7, the glass manufacturing apparatus **1** may include a first heat exchanger **77** and a second heat transport line **78**. The first heat exchanger **77** is provided along a connection line **74** and is thermally connected to a first reactor **71** via a second heat transport line **78**.

[0120] The first reactor **71** heats a heat medium (e.g., air) using heat produced in a methanation reaction. The first reactor **71** does not mix the reactant or product of the methanation reaction with the heat medium and transfers heat therebetween. The second heat transport line **78** transports the heat medium heated in the first reactor **71** to the first heat exchanger **77**.

[0121] The first heat exchanger **77** heats the product of the first reactor **71** with the H.sub.2O concentration adjusted in the water vapor controller **73** using the heat produced in the methanation reaction before the product is supplied to the second reactor **72**. The heat produced by the methanation reaction can be effectively used to reduce the specific energy consumption of molten glass. The specific energy consumption is a consumption amount of energy input from outside the system to produce 1 ton of molten glass. The first heat exchanger **77** does not mix the product of the first reactor **71** with the heat medium and transfers heat therebetween.

[0122] In addition, the heat produced by the methanation reaction may be used in a different field. For example, the first heat exchanger **77** may be provided along the second supply line **22** to preheat the oxidizing gas (e.g., pure oxygen gas). Heat produced in the methanation reaction may not be used inside the system or may be used outside the system.

[0123] A fifth embodiment of a glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. 8. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. 4 will be mainly described. As shown in FIG. 8, the glass manufacturing apparatus **1** preferably includes a second heat exchanger **23**.

[0124] The second heat exchanger **23** is provided along the second supply line **22** and preheats a oxidizing gas (e.g., pure oxygen gas) through heat exchange with a heat medium heated by the recuperator **60**. Heat collected from a combustion gas can be effectively used to reduce the specific energy consumption of molten glass. The second heat exchanger **23** does not mix the oxidizing gas with the heat medium (e.g., air) and transfers heat therebetween.

[0125] The first heat transport line **80** transports the heat medium from the recuperator **60** to the second heat exchanger **23**. Preferably, the first heat transport line **80** transports the heat medium from the recuperator **60** to the second reactor **72** and then transports the heat medium from the

second reactor **72** to the second heat exchanger **23**. Before the oxidizing gas is heated, the reactant of the second reactor **72** can be heated to easily secure heat necessary to perform a reaction in the second reactor **72**.

[0126] A sixth embodiment of a glass manufacturing apparatus **1** including a recuperator **60** will be described with reference to FIG. **9**. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **4** will be mainly described. As shown in FIG. **9**, the glass manufacturing apparatus **1** preferably includes a third heat exchanger **24** and a second dehydration unit **25**.

[0127] The third heat exchanger **24** transfers heat from the product of the second reactor **72** to the oxidizing gas at a first point of the first supply line **21** overlapping the second supply line **22**. The third heat exchanger **24** does not mix the product of the second reactor **72** with the oxidizing gas and transfers heat therebetween. The second dehydration unit **25** removes the H.sub.2O gas from the product of the second reactor **72** at a second point located downstream from the first point of the first supply line **21**. Although it is only necessary for the second dehydration unit **25** to remove at least a part of the H.sub.2O gas, substantially all of the H.sub.2O gas is removed in the present embodiment.

[0128] The second dehydration unit **25** removes the H.sub.2O gas from the product of the second reactor **72**, for example, by cooling the product of the second reactor **72**. The H.sub.2O gas not only does not produce heat of combustion but also ineffectively consumes heat of combustion. The second dehydration unit **25** limits the supply of the H.sub.2O gas to the burner **20**. It is possible to efficiently heat glass with combustion heat without ineffectively heating H.sub.2O gas not contributing to combustion. Moreover, the H.sub.2O gas concentration in the furnace atmosphere can be reduced.

[0129] Before the second dehydration unit **25** cools the product of the second reactor **72**, the third heat exchanger **24** transfers heat from the product of the second reactor **72** to the oxidizing gas. Thereby, heat collected from the combustion gas can be used efficiently, thereby reducing the specific energy consumption of the molten glass.

[0130] A first embodiment of a glass manufacturing apparatus **1** including a first regenerator **90A** and a second regenerator **90B** will be described with reference to FIG. **10**. The glass manufacturing apparatus **1** includes a glass melting furnace **10**, a first burner **20A**, a second burner **20B**, the first regenerator **90A**, the second regenerator **90B**, and a first reactor **71**. A gas transformer **30** includes the first regenerator **90A**, the second regenerator **90B**, the first reactor **71**, or the like (including an water vapor controller **73** and an additive line **75** to be described below). The first reactor **71** performs a methanation reaction and the first regenerator **90A** and the second regenerator **90B** perform at least one of DRM and STR reactions. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **1** will be mainly described.

[0131] The first regenerator **90A** and the second regenerator **90B** are used in combination with the first burner **20A** and the second burner **20B**. Although the number of first regenerators **90A** is one in FIG. **10**, the number of first regenerators **90A** may be two or more. Likewise, it is only necessary for the number of second regenerators **90B**, the number of first burners **20A**, and the number of second burners **20B** to be one or more.

[0132] The glass manufacturing apparatus **1** alternately and iteratively performs a process in which the first burner **20A** forms a flame inside the glass melting furnace **10** and the second burner **20B** forms a flame inside the glass melting furnace **10**. FIG. **10** is a diagram showing a state in which the first burner **20A** forms a flame inside the glass melting furnace **10**.

[0133] The first regenerator **90A** collects heat from a combustion gas emitted from the glass melting furnace **10** while the second burner **20B** forms a flame inside the glass melting furnace **10**. The first regenerator **90A** produces CO gas from the product of the first reactor **71** by releasing the heat collected in advance and performing at least one of the DRM and STR reactions while the first burner **20A** forms a flame inside the glass melting furnace **10**. The first burner **20A** burns a flammable gas containing the CO gas produced by the first regenerator **90A** and a oxidizing gas to

form a flame inside the glass melting furnace **10**.

[0134] Likewise, the second regenerator **90B** collects heat from the combustion gas emitted from the glass melting furnace **10** while the first burner **20A** forms a flame inside the glass melting furnace **10**. The second regenerator **90B** produces the CO gas from the product of the first reactor **71** by releasing the heat collected in advance and performing at least one of the DRM and STR reactions while the second burner **20B** forms a flame inside the glass melting furnace **10**. The second burner **20B** burns the flammable gas containing the CO gas produced by the second regenerator **90B** and the oxidizing gas to form a flame inside the glass melting furnace **10**.

[0135] Unlike the recuperator **60** and the first reactor **71**, the first regenerator **90A** and the second regenerator **90B** direct the flow of combustion gas. The heat of the combustion gas is accumulated in the structures of the first regenerator **90A** and the second regenerator **90B**.

[0136] The first regenerator **90A** and the second regenerator **90B** produce CO gas from the product of the first reactor **71** by performing at least one of the DRM and STR reactions. When both the DRM and STR reactions occur, CH₄ and H₂O gases and CO₂ gas are reactants and CO and H₂ gases are products (see Eqs. (5) and (6)). The product may include a gas other than the CO gas and the H₂ gas, for example, at least one of H₂O gas, CO₂ gas, and CH₄ gas.

[0137] Because the DRM reaction and the STR reaction are endothermic reactions, heat can be efficiently collected from the heat medium and heat collected from the combustion gas can be used efficiently. Moreover, the product of the endothermic reaction (the CO gas) potentially contains more heat than the reactant of the endothermic reaction (the H₂ gas). Therefore, the combustion of the CO gas can improve the heat of combustion per mole (see Eqs. (7) and (8)) as compared to the combustion of the H₂ gas.

[0138] It is only necessary for the reactions occurring in the first regenerator **90A** and the second regenerator **90B** to be endothermic reactions as a whole. The reactions occurring in the first regenerator **90A** and the second regenerator **90B** may include reactions other than DRM reactions and STR reactions. Therefore, in the first regenerator **90A** and the second regenerator **90B**, the reactants and products are not particularly limited.

[0139] The glass manufacturing apparatus **1** includes a water vapor controller **73**. The water vapor controller **73** is provided along a connection line **74** connecting the first reactor **71** and the first regenerator **90A**. The water vapor controller **73** adjusts an H₂O concentration in the product of the first reactor **71** by removing at least a part of the H₂O gas from the product of the first reactor **71**. The water vapor controller **73** is removed, for example, by cooling and liquefying the H₂O gas. The first regenerator **90A** produces CO gas from the product of the first reactor **71** in which the H₂O concentration is adjusted by the water vapor controller **73**.

[0140] In the present embodiment, the water vapor controller **73** removes at least a part of the H₂O gas from the product of the first reactor **71** and then delivers the product of the first reactor **71** to the first regenerator **90A**. The H₂O concentration in the product of the first regenerator **90A** can be reduced and the H₂O concentration in the furnace atmosphere of the glass melting furnace **10** can be reduced.

[0141] A process of removing at least a part of the H₂O gas from the product of the first reactor **71** and then delivering the product of the first reactor **71** to the first regenerator **90A** is also effective in performing the overall reaction represented by Eq. (1) or (2). This is evident from the fact that H₂O does not appear as the substance (reactant) on the left side of the general reaction equation, but is present as the substance (product) on the right side of the general reaction equation. By performing the above-described overall reaction and endothermic reaction, the heat collection rate can be improved.

[0142] Although the connection line **74** may remove at least a part of the H₂O gas from the product of the first reactor **71** in the water vapor controller **73** and then deliver the product of the first reactor **71** to the first regenerator **90A**, the product may be delivered to the second regenerator

90B instead of the first regenerator **90A**. In addition, the connection line **74** connecting the first reactor **71** and the first regenerator **90A** and the connection line **74** connecting the first reactor **71** and the second regenerator **90B** may be different or may be provided separately.

[0143] Preferably, the amount of H.sub.2O gas removal in the water vapor controller **73** is set so that C is not produced as a byproduct in the first regenerator **90A** (or so that soot is not deposited). Specifically, the water vapor controller **73** preferably removes only a part of the H.sub.2O gas from the product of the first reactor **71** so that the following Inequality (b1) is valid when a reaction temperature in the first regenerator **90A** is 900° C. or higher, the following Inequality (b2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (b3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C. while the first burner **20A** forms the flame inside the glass melting furnace **10**.

[00007] $b \geq -a + 1$ (b1) $b \geq -0.68a + 1.01$ (b2) $b \geq -0.1143a^2 + 0.0286a + 1.3029$ (b3)

[0144] In the above Inequalities (b1), (b2), and (b3), a denotes a molar ratio (CO.sub.2/CH.sub.4) of the CO.sub.2 gas supplied to the first regenerator **90A** to the CH.sub.4 gas supplied to the first regenerator **90A** and b denotes a molar ratio (H.sub.2O/CH.sub.4) of the H.sub.2O gas supplied to the first regenerator **90A** to the CH.sub.4 gas supplied to the first regenerator **90A**.

[0145] More preferably, the following Inequality (b4) is valid in addition to any one of the above-described Inequalities (b1), (b2), and (b3).

[00008] $b \leq 2a$ (b4)

[0146] If the above Inequality (b4) is valid, an H.sub.2O gas concentration in the combustion gas of the first burner **20A** is 67% or less by volume. It has been confirmed that if the H.sub.2O gas concentration in the combustion gas is 67% or less by volume, there is no problem with the quality of the glass product or corrosion of the furnace material.

[0147] In addition to any one of the above Inequalities (b1), (b2), and (b3), the following Inequality (b5) may be valid.

[00009] $b \geq -a + 3$ (b5)

[0148] The first regenerator **90A** does not have a metal catalyst. Therefore, the following Inequality (b6) may be valid instead of the above-described Inequality (b5).

[00010] $b < -a + 3$ (b6)

[0149] If the above Inequality (b6) is valid, the amount of H.sub.2O gas removal in the water vapor controller **73** is high and the H.sub.2O gas concentration in the combustion gas is low.

[0150] Likewise, preferably, the amount of H.sub.2O gas removal in the water vapor controller **73** is set so that C is not produced as a byproduct in the second regenerator **90B** (or so that soot is not deposited). Specifically, the water vapor controller **73** removes only a part of the H.sub.2O gas from the product of the first reactor **71** so that the following Inequality (c1) is valid when a reaction temperature in the second regenerator **90B** is 900° C. or higher (preferably 1600° C. or lower), the following Inequality (c2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (c3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C. while the second burner **20B** forms the flame inside the glass melting furnace **10**.

[00011] $b \geq -a + 1$ (c1) $b \geq -0.68a + 1.01$ (c2) $b \geq -0.1143a^2 + 0.0286a + 1.3029$ (c3)

[0151] In the above Inequalities (c1), (c2), and (c3), a denotes a molar ratio (CO.sub.2/CH.sub.4) of the CO.sub.2 gas supplied to the second regenerator **90B** to the CH.sub.4 gas supplied to second regenerator **90B** and b denotes a molar ratio (H.sub.2O/CH.sub.4) of the H.sub.2O gas supplied to the second regenerator **90B** to the CH.sub.4 gas supplied to the second regenerator **90B**.

[0152] More preferably, the following Inequality (c4) is valid in addition to any one of the above-described Inequalities (c1), (c2), and (c3).

[00012] $b \leq 2a$ (c4)

[0153] If the above Inequality (c4) is valid, an H.sub.2O gas concentration in the combustion gas of the second burner **20B** is 67% or less by volume. It has been confirmed that if the H.sub.2O gas concentration in the combustion gas is 67% or less by volume, there is no problem with the quality of the glass product or corrosion of the furnace material.

[0154] In addition to any one of the above Inequalities (c1), (c2), and (c3), the following Inequality (c5) may be valid.

[00013] $b \geq -a + 3$ (c5)

[0155] The second regenerator **90B** does not have a metal catalyst. Therefore, the following Inequality (c6) may be valid instead of the above-described Inequality (c5).

[00014] $b < -a + 3$ (c6)

[0156] If the above Inequality (c6) is valid, the amount of H.sub.2O gas removal in the water vapor controller **73** is high and the H.sub.2O gas concentration in the combustion gas is low.

[0157] The glass manufacturing apparatus **1** preferably includes an additive line **75**. The additive line **75** supplies at least a part of the CO.sub.2 gas for use in the DRM reaction to the first regenerator **90A** without passing through the first reactor **71**. Thereby, it is possible to reduce the molar ratio x in the first reactor **71** and suppress the deposition of soot in the first reactor **71**.

[0158] The additive line **75** branches from a circulation line **50**, which will be discussed below, for example, to bypass the first reactor **71** and join the connection line **74**. The additive line **75** may bypass not only the first reactor **71** but also the water vapor controller **73**. Cooling of the CO.sub.2 gas can be suppressed by the water vapor controller **73**. A flow rate controller **76** may be provided along the additive line **75**.

[0159] Although the additive line **75** joins a connection line **74**, the additive line **75** may be connected to the first regenerator **90A** without joining the connection line **74**. In the former case, the product of the first reactor **71** and the CO.sub.2 gas are premixed and supplied to the first regenerator **90A**. In the latter case, the product of the first reactor **71** and the CO.sub.2 gas are separately supplied to the first regenerator **90A**.

[0160] Although the additive line **75** supplies at least a part of the CO.sub.2 gas for use in the DRM reaction to the first regenerator **90A** without passing through the first reactor **71**, it may be supplied to the second regenerator **90B** instead of the first regenerator **90A**. In addition, the additive line **75** for supplying the CO.sub.2 gas to the first regenerator **90A** and the additive line **75** for supplying the CO.sub.2 gas to the second regenerator **90B** may be different from each other or may be provided separately.

[0161] The glass manufacturing apparatus **1** preferably includes a circulation line **50**. The circulation line **50** supplies at least a part of the CO.sub.2 gas contained in the combustion gas emitted from the glass melting furnace **10** from the second regenerator **90B** to the first reactor **71**. At least the part of the CO.sub.2 gas emitted from the glass melting furnace **10** can be used as a reactant in the methanation reaction. The CO.sub.2 gas can be circulated and an amount of CO.sub.2 gas to be emitted can be reduced. At least the part of the CO.sub.2 gas emitted from the glass melting furnace **10** can also be used as a reactant in the DRM or STR reaction.

[0162] The circulation line **50** may supply at least the part of the CO.sub.2 gas contained in the combustion gas emitted from the glass melting furnace **10** from the first regenerator **90A** to the first reactor **71**. In addition, the circulation line **50** for delivering the CO.sub.2 gas from the second regenerator **90B** to the first reactor **71** and the circulation line **50** for delivering the CO.sub.2 gas from the first regenerator **90A** to the first reactor **71** may be different or may be provided separately.

[0163] The glass manufacturing apparatus **1** may include a first dehydration unit **51** along the circulation line **50**. The first dehydration unit **51** separates the H.sub.2O gas from the CO.sub.2 gas by removing the H.sub.2O gas from the combustion gas. It is possible to restrict the circulation of the H.sub.2O gas while permitting the circulation of CO.sub.2 gas. The H.sub.2O gas not only does

not produce heat of combustion but also ineffectively consumes heat of combustion. If the circulation of the H.sub.2O gas can be restricted, it is possible to efficiently heat glass with combustion heat without ineffectively heating H.sub.2O gas not contributing to combustion. Moreover, if the circulation of the H.sub.2O gas can be restricted, the H.sub.2O gas concentration in the furnace atmosphere can be reduced.

[0164] Although it is only necessary for the first dehydration unit **51** to remove at least a part of the H.sub.2O gas, substantially all of the H.sub.2O gas is removed in the present embodiment. In addition, when only a part of the H.sub.2O gas is removed from the first dehydration unit **51** or when there is no first dehydration unit **51** as described below, the gas containing the H.sub.2O gas is supplied to the first reactor **71**.

[0165] More preferably, a desulfurization unit **52** is provided along the circulation line **50**. The desulfurization unit **52** removes a sulfur-containing gas from the combustion gas. The sulfur contained in the sulfur-containing gas is derived from a glass raw material, for example, a fining agent. The supply of the sulfur-containing gas to the first reactor **71** can be restricted by providing the desulfurization unit **52** along the circulation line **50**.

[0166] A second embodiment of a glass manufacturing apparatus **1** including a first regenerator **90A** and a second regenerator **90B** will be described with reference to FIG. **11**. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **10** will be mainly described. As shown in FIG. **11**, the glass manufacturing apparatus **1** may not include the first dehydration unit **51** (see FIG. **10**). The water vapor controller **73** may also serve as the first dehydration unit **51**.

[0167] A third embodiment of a glass manufacturing apparatus **1** including a first regenerator **90A** and a second regenerator **90B** will be described with reference to FIG. **12**. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **10** will be mainly described. As shown in FIG. **12**, the water vapor controller **73** may include a dehydration unit **73a** for removing a part of the H.sub.2O gas by cooling and liquefying and a bypass line **73b** for delivering the remaining part of the H.sub.2O gas from the first reactor **71** to the first regenerator **90A** (or the second regenerator **90B**).

[0168] According to the present embodiment, all unnecessary H.sub.2O gas can be removed in the dehydration unit **73a** while the H.sub.2O gas for use in the STR reaction remains. Moreover, the H.sub.2O gas for use in the STR reaction can also be delivered from the first reactor **71** to the first regenerator **90A** (or the second regenerator **90B**) without cooling in the dehydration unit **73a**. The bypass line **73b** bypasses the dehydration unit **73a**. A flow rate controller **73c** may be provided along the bypass line **73b**.

[0169] A fourth embodiment of a glass manufacturing apparatus **1** including a first regenerator **90A** and a second regenerator **90B** will be described with reference to FIG. **13**. Hereinafter, differences from the glass manufacturing apparatus **1** shown in FIG. **10** will be mainly described. As shown in FIG. **13**, the glass manufacturing apparatus **1** may include a first heat exchanger **77** and a second heat transport line **78**. The first heat exchanger **77** is provided along a connection line **74** and is thermally connected to a first reactor **71** via a second heat transport line **78**.

[0170] The first reactor **71** heats a heat medium (e.g., air) using heat produced in a methanation reaction. The first reactor **71** does not mix the reactant or product of the methanation reaction with the heat medium and transfers heat therebetween. The second heat transport line **78** transports the heat medium heated in the first reactor **71** to the first heat exchanger **77**.

[0171] The first heat exchanger **77** heats the product of the first reactor **71** with the H.sub.2O concentration adjusted in the water vapor controller **73** using the heat produced in the methanation reaction before the product is supplied to the first regenerator **90A** (or the second regenerator **90B**). The heat produced by the methanation reaction can be effectively used to reduce the specific energy consumption of molten glass. The first heat exchanger **77** does not mix the product of the first reactor **71** with the heat medium and transfers heat therebetween.

[0172] In addition, the heat produced by the methanation reaction may be used in a different field.

For example, the first heat exchanger 77 may be provided along the second supply line 22 to preheat the oxidizing gas (e.g., pure oxygen gas). Heat produced in the methanation reaction may not be used inside the system or may be used outside the system.

[0173] The following appendixes are disclosed with respect to the above-described embodiments and the like.

[Appendix 1] A glass manufacturing apparatus including: [0174] a recuperator configured to heat a heat medium through heat exchange with a combustion gas emitted from a glass melting furnace; [0175] a first reactor configured to produce CH_4 gas and H_2O gas from CO_2 gas and H_2 gas by performing a methanation reaction; [0176] an water vapor controller configured to adjust an H_2O concentration in a product of the first reactor by removing at least a part of the H_2O gas from the product of the first reactor; [0177] a second reactor configured to produce CO gas and H_2 gas from the product of the first reactor with the H_2O concentration adjusted in the water vapor controller by performing at least one of a dry reforming reaction and a steam reforming reaction through heat exchange with the heat medium heated by the recuperator; and [0178] a burner configured to form a flame in the glass melting furnace by burning a oxidizing gas and a flammable gas containing the CO gas and the H_2 gas produced by the second reactor.

[Appendix 2] The glass manufacturing apparatus according to appendix 1, [0179] wherein the water vapor controller removes only a part of the H_2O gas from the product of the first reactor so that the following Inequality (a1) is valid when a reaction temperature in the second reactor is 900°C . or higher, the following Inequality (a2) is valid when the reaction temperature is 800°C . or higher and lower than 900°C ., and the following Inequality (a3) is valid when the reaction temperature is 700°C . or higher and lower than 800°C ., and [0180] wherein, in the following Inequalities (a1), (a2), and (a3), a denotes a molar ratio (CO_2/CH_4) of the CO_2 gas supplied to the second reactor to the CH_4 gas supplied to the second reactor and b denotes a molar ratio ($\text{H}_2\text{O}/\text{CH}_4$) of the H_2O gas supplied to the second reactor to the CH_4 gas supplied to the second reactor.

[00015] $b \geq -a + 1$ (a1) $b \geq -0.68a + 1.01$ (a2) $b \geq -0.1143a^2 + 0.0286a + 1.3029$ (a3)

[Appendix 3] The glass manufacturing apparatus according to appendix 2, wherein the water vapor controller removes only a part of the H_2O gas from the product of the first reactor so that the following Inequality (a4) is valid in addition to any one of the above Inequalities (a1), (a2), and (a3).

[00016] $b \leq 2a$ (a4)

[Appendix 4] The glass manufacturing apparatus according to any one of appendixes 1 to 3, including an additive line along which at least a part of the CO_2 gas for use in the dry reforming reaction is supplied to the second reactor without passing through the first reactor.

[Appendix 5] The glass manufacturing apparatus according to any one of appendixes 1 to 4, including a first heat exchanger configured to heat the product of the first reactor with the H_2O concentration adjusted in the water vapor controller using heat produced by the methanation reaction before the product of the first reactor is supplied to the second reactor.

[Appendix 6] The glass manufacturing apparatus according to any one of appendixes 1 to 5, wherein the oxidizing gas is pure oxygen gas or oxygen-enriched air.

[Appendix 7] The glass manufacturing apparatus according to any one of appendixes 1 to 6, including a circulation line along which at least a part of the CO_2 gas contained in a combustion gas burned by the burner is supplied from the glass melting furnace to the first reactor.

[Appendix 8] The glass manufacturing apparatus according to appendix 7, including a first dehydration unit configured to remove the H_2O gas from the combustion gas along the circulation line.

[Appendix 9] The glass manufacturing apparatus according to any one of appendixes 1 to 8,

including a second heat exchanger configured to preheat the oxidizing gas through the heat exchange with the heat medium heated by the recuperator.

[Appendix 10] The glass manufacturing apparatus according to any one of appendixes 1 to 9, including: [0181] a first supply line along which a product of the second reactor is supplied to the burner; [0182] a second supply line along which the oxidizing gas is supplied to the burner; [0183] a third heat exchanger configured to transfer heat from the product of the second reactor to the oxidizing gas at a first point of the first supply line overlapping the second supply line; and [0184] a second dehydration unit configured to remove the H.sub.2O gas from the product of the second reactor at a second point located downstream from the first point of the first supply line.

[Appendix 11] The glass manufacturing apparatus according to any one of appendixes 1 to 10, wherein the second reactor has a metal catalyst that promotes at least one of the dry reforming reaction and the steam reforming reaction.

[Appendix 12] A glass manufacturing apparatus for alternately and iteratively performing a process in which a first burner forms a flame inside a glass melting furnace and a second burner forms a flame inside the glass melting furnace, the glass manufacturing apparatus including: [0185] a first reactor configured to produce CH.sub.4 gas and H.sub.2O gas from CO.sub.2 gas and H.sub.2 gas by performing a methanation reaction; [0186] an water vapor controller configured to adjust an H.sub.2O concentration in a product of the first reactor by removing at least a part of the H.sub.2O gas from the product of the first reactor; [0187] a first regenerator configured to produce CO gas and the H.sub.2 gas from the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller by collecting heat from a combustion gas emitted from the glass melting furnace while the second burner forms the flame inside the glass melting furnace, releasing the heat while the first burner forms the flame inside the glass melting furnace, and performing at least one of a dry reforming reaction and a steam reforming reaction; [0188] the first burner configured to form the flame inside the glass melting furnace by burning a flammable gas containing the CO gas and the H.sub.2 gas produced in the first regenerator and a oxidizing gas; [0189] a second regenerator configured to produce the CO gas and the H.sub.2 gas from the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller by collecting heat from a combustion gas emitted from the glass melting furnace while the first burner forms the flame inside the glass melting furnace, releasing the heat while the second burner forms the flame inside the glass melting furnace, and performing at least one of the dry reforming reaction and the steam reforming reaction; and [0190] the second burner configured to form the flame inside the glass melting furnace by burning the flammable gas containing the CO gas and the H.sub.2 gas produced in the second regenerator and the oxidizing gas.

[Appendix 13] The glass manufacturing apparatus according to appendix 12, [0191] wherein the water vapor controller removes only a part of the H.sub.2O gas from the product of the first reactor so that the following Inequality (b1) is valid when a reaction temperature in the first regenerator is 900° C. or higher, the following Inequality (b2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (b3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C. while the first burner forms the flame inside the glass melting furnace, and [0192] wherein, in the following Inequalities (b1), (b2), and (b3), a denotes a molar ratio (CO.sub.2/CH.sub.4) of the CO.sub.2 gas supplied to the first regenerator to the CH.sub.4 gas supplied to the first regenerator and b denotes a molar ratio (H.sub.2O/CH.sub.4) of the H.sub.2O gas supplied to the first regenerator to the CH.sub.4 gas supplied to the first regenerator.

[00017] $b \geq -a + 1$ (b1) $b \geq -0.68a + 1.01$ (b2) $b \geq -0.1143a^2 + 0.0286a + 1.3029$ (b3)

[Appendix 14] The glass manufacturing apparatus according to appendix 13, wherein the water vapor controller removes only a part of the H.sub.2O gas from the product of the first reactor so that the following Inequality (b4) is valid in addition to any one of the above Inequalities (b1), (b2),

and (b3).

[00018] $b \leq 2a$ (b4)

[Appendix 15] The glass manufacturing apparatus according to any one of appendixes 12 to 14, including an additive line along which at least a part of the CO.sub.2 gas for use in the dry reforming reaction is supplied to the first regenerator or the second regenerator without passing through the first reactor.

[Appendix 16] The glass manufacturing apparatus according to any one of appendixes 12 to 15, including a first heat exchanger configured to heat the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller using heat produced by the methanation reaction before the product of the first reactor is supplied to the first regenerator or the second regenerator.

[Appendix 17] The glass manufacturing apparatus according to any one of appendixes 12 to 16, wherein the oxidizing gas is pure oxygen gas or oxygen-enriched air.

[Appendix 18] The glass manufacturing apparatus according to any one of appendixes 12 to 17, including a circulation line along which at least a part of the CO.sub.2 gas contained in a combustion gas emitted from the glass melting furnace is supplied from the second regenerator or the first regenerator to the first reactor.

[Appendix 19] The glass manufacturing apparatus according to appendix 18, including a dehydration unit configured to remove the H.sub.2O gas from the combustion gas along the circulation line.

[Appendix 20] A glass manufacturing method including manufacturing molten glass using the glass manufacturing apparatus according to any one of appendixes 1 to 19.

[0193] Although the glass manufacturing apparatus and the glass manufacturing method according to the present disclosure have been described above, the present disclosure is not limited to the above-described embodiments and the like. Various changes, modifications, substitutions, additions, deletions, and combinations can be made without departing from the scope described in the claims. These are, of course, also within the technical scope of the present disclosure.

[0194] Priority is claimed on Japanese Patent Application No. 2022-188270, filed Nov. 25, 2022, the content of which is incorporated herein by reference.

REFERENCE SIGNS LIST

[0195] **1** Glass manufacturing apparatus [0196] **10** Glass melting furnace [0197] **20** Burner [0198] **60** Recuperator [0199] **71** First reactor [0200] **72** Second reactor [0201] **73** Water vapor controller

Claims

1. A glass manufacturing apparatus comprising: a recuperator configured to heat a heat medium through heat exchange with a combustion gas emitted from a glass melting furnace; a first reactor configured to produce CH.sub.4 gas and H.sub.2O gas from CO.sub.2 gas and H.sub.2 gas by performing a methanation reaction; an water vapor controller configured to adjust an H.sub.2O concentration in a product of the first reactor by removing at least a part of the H.sub.2O gas from the product of the first reactor; a second reactor configured to produce CO gas and H.sub.2 gas from the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller by performing at least one of a dry reforming reaction and a steam reforming reaction through heat exchange with the heat medium heated by the recuperator; and a burner configured to form a flame in the glass melting furnace by burning a oxidizing gas and a flammable gas containing the CO gas and the H.sub.2 gas produced by the second reactor.

2. The glass manufacturing apparatus according to claim 1, wherein the water vapor controller removes only a part of the H.sub.2O gas from the product of the first reactor so that the following Inequality (a1) is valid when a reaction temperature in the second reactor is 900° C. or higher, the

following Inequality (a2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (a3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C., and wherein, in the following Inequalities (a1), (a2), and (a3), a denotes a molar ratio ($\text{CO.sub.2}/\text{CH.sub.4}$) of the CO.sub.2 gas supplied to the second reactor to the CH.sub.4 gas supplied to the second reactor and b denotes a molar ratio ($\text{H.sub.2O}/\text{CH.sub.4}$) of the H.sub.2O gas supplied to the second reactor to the CH.sub.4 gas supplied to the second reactor. $b \geq -a + 1$ (a1) $b \geq -0.68a + 1.01$ (a2)

$$b \geq -0.1143a^2 + 0.0286a + 1.3029. \quad (\text{a3})$$

3. The glass manufacturing apparatus according to claim 2, wherein the water vapor controller removes only a part of the H.sub.2O gas from the product of the first reactor so that the following Inequality (a4) is valid in addition to any one of the above Inequalities (a1), (a2), and (a3).

$$b \leq 2a. \quad (\text{a4})$$

4. The glass manufacturing apparatus according to any claim 1, comprising an additive line along which at least a part of the CO.sub.2 gas for use in the dry reforming reaction is supplied to the second reactor without passing through the first reactor.

5. The glass manufacturing apparatus according to claim 1, comprising a first heat exchanger configured to heat the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller using heat produced by the methanation reaction before the product of the first reactor is supplied to the second reactor.

6. The glass manufacturing apparatus according to claim 1, wherein the oxidizing gas is pure oxygen gas or oxygen-enriched air.

7. The glass manufacturing apparatus according to claim 1, comprising a circulation line along which at least a part of the CO.sub.2 gas contained in a combustion gas burned by the burner is supplied from the glass melting furnace to the first reactor.

8. The glass manufacturing apparatus according to claim 7, comprising a first dehydration unit configured to remove the H.sub.2O gas from the combustion gas along the circulation line.

9. The glass manufacturing apparatus according to claim 1, comprising a second heat exchanger configured to preheat the oxidizing gas through the heat exchange with the heat medium heated by the recuperator.

10. The glass manufacturing apparatus according to claim 1, comprising: a first supply line along which a product of the second reactor is supplied to the burner; a second supply line along which the oxidizing gas is supplied to the burner; a third heat exchanger configured to transfer heat from the product of the second reactor to the oxidizing gas at a first point of the first supply line overlapping the second supply line; and a second dehydration unit configured to remove the H.sub.2O gas from the product of the second reactor at a second point located downstream from the first point of the first supply line.

11. The glass manufacturing apparatus according to any claim 1, wherein the second reactor has a metal catalyst that promotes at least one of the dry reforming reaction and the steam reforming reaction.

12. A glass manufacturing apparatus for alternately and iteratively performing a process in which a first burner forms a flame inside a glass melting furnace and a second burner forms a flame inside the glass melting furnace, the glass manufacturing apparatus comprising: a first reactor configured to produce CH.sub.4 gas and H.sub.2O gas from CO.sub.2 gas and H.sub.2 gas by performing a methanation reaction; an water vapor controller configured to adjust an H.sub.2O concentration in a product of the first reactor by removing at least a part of the H.sub.2O gas from the product of the first reactor; a first regenerator configured to produce CO gas and the H.sub.2 gas from the product of the first reactor with the H.sub.2O concentration adjusted in the water vapor controller by collecting heat from a combustion gas emitted from the glass melting furnace while the second burner forms the flame inside the glass melting furnace, releasing the heat while the first burner

forms the flame inside the glass melting furnace, and performing at least one of a dry reforming reaction and a steam reforming reaction; the first burner configured to form the flame inside the glass melting furnace by burning a flammable gas containing the CO gas and the H₂ gas produced in the first regenerator and an oxidizing gas; a second regenerator configured to produce the CO gas and the H₂ gas from the product of the first reactor with the H₂O concentration adjusted in the water vapor controller by collecting heat from a combustion gas emitted from the glass melting furnace while the first burner forms the flame inside the glass melting furnace, releasing the heat while the second burner forms the flame inside the glass melting furnace, and performing at least one of the dry reforming reaction and the steam reforming reaction; and the second burner configured to form the flame inside the glass melting furnace by burning the flammable gas containing the CO gas and the H₂ gas produced in the second regenerator and the oxidizing gas.

13. The glass manufacturing apparatus according to claim 12, wherein the water vapor controller removes only a part of the H₂O gas from the product of the first reactor so that the following Inequality (b1) is valid when a reaction temperature in the first regenerator is 900° C. or higher, the following Inequality (b2) is valid when the reaction temperature is 800° C. or higher and lower than 900° C., and the following Inequality (b3) is valid when the reaction temperature is 700° C. or higher and lower than 800° C. while the first burner forms the flame inside the glass melting furnace, and wherein, in the following Inequalities (b1), (b2), and (b3), a denotes a molar ratio (CO₂/CH₄) of the CO₂ gas supplied to the first regenerator to the CH₄ gas supplied to the first regenerator and b denotes a molar ratio (H₂O/CH₄) of the H₂O gas supplied to the first regenerator to the CH₄ gas supplied to the first regenerator.

$$b \geq -a + 1 \quad (b1) \quad b \geq -0.68a + 1.01 \quad (b2) \quad b \geq -0.1143a^2 + 0.0286a + 1.3029. \quad (b3)$$

14. The glass manufacturing apparatus according to claim 13, wherein the water vapor controller removes only a part of the H₂O gas from the product of the first reactor so that the following Inequality (b4) is valid in addition to any one of the above Inequalities (b1), (b2), and (b3).

$$b \leq 2a. \quad (b4)$$

15. The glass manufacturing apparatus according to claim 12, comprising an additive line along which at least a part of the CO₂ gas for use in the dry reforming reaction is supplied to the first regenerator or the second regenerator without passing through the first reactor.

16. The glass manufacturing apparatus according to claim 12, comprising a first heat exchanger configured to heat the product of the first reactor with the H₂O concentration adjusted in the water vapor controller using heat produced by the methanation reaction before the product of the first reactor is supplied to the first regenerator or the second regenerator.

17. The glass manufacturing apparatus according to claim 12, wherein the oxidizing gas is pure oxygen gas or oxygen-enriched air.

18. The glass manufacturing apparatus according to claim 12, comprising a circulation line along which at least a part of the CO₂ gas contained in a combustion gas emitted from the glass melting furnace is supplied from the second regenerator or the first regenerator to the first reactor.

19. The glass manufacturing apparatus according to claim 18, comprising a dehydration unit configured to remove the H₂O gas from the combustion gas along the circulation line.

20. A glass manufacturing method comprising manufacturing molten glass using the glass manufacturing apparatus according to claim 1.
