

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12385166
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Chen; Hongbo et al.

Device and method for twisting electrostatic spinning superfine fiber

Abstract

Disclosed is a device for twisting electrostatic spinning superfine fiber. The device comprises an outer sleeve and a middle sleeve, wherein the outer sleeve sleeves the middle sleeve, an annular gap is formed between the outer sleeve and the middle sleeve, a melt inlet communicating with the annular gap is formed in the outer sleeve, a conical hole is formed in the bottom end of the outer sleeve, the top end of the conical hole communicates with the bottom end of the annular gap, and the outer sleeve is wrapped with a heating ring used for heating a melt in the annular gap; a cylindrical metal rod is arranged in the middle sleeve in a penetrating mode, an interval is formed between the metal rod and the middle sleeve, the bottom end of the metal rod is fixedly connected with a circular truncated cone located below the conical hole.

Inventors:	Chen; Hongbo (Qingdao, CN), Han; Wenwen (Qingdao, CN), Yang; Weimin (Qingdao, CN), Liu; Haichao (Qingdao, CN), Liang; Hui (Qingdao, CN), Wang; Chuansheng (Qingdao, CN)
Applicant:	QINGDAO UNIVERSITY OF SCIENCE AND TECHNOLOGY (Qingdao, CN)
Family ID:	77379653
Assignee:	QINGDAO UNIVERSITY OF SCIENCE AND TECHNOLOGY (Qingdao, CN)
Appl. No.:	17/905948
Filed (or PCT Filed):	July 19, 2021
PCT No.:	PCT/CN2021/107034
PCT Pub. No.:	WO2022/267119
PCT Pub. Date:	December 29, 2022

Prior Publication Data

Document Identifier

US 20230407530 A1

Publication Date

Dec. 21, 2023

Foreign Application Priority Data

CN

202110691029.9

Jun. 22, 2021

Publication Classification

Int. Cl.: D01H1/08 (20060101); D01D5/00 (20060101); D01H1/26 (20060101)

U.S. Cl.:

CPC D01H1/08 (20130101); D01D5/0069 (20130101); D01D5/0076 (20130101);
D01D5/0092 (20130101); D01H1/26 (20130101);

Field of Classification Search

CPC: D01H (1/08); D01H (1/26); D01D (5/18); D01D (5/0092); D01D (5/0069); D01D (5/0076); Y02P (70/62)

References Cited

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
101302682	12/2007	CN	N/A
104358029	12/2014	CN	N/A
106283219	12/2016	CN	N/A
109594135	12/2018	CN	N/A
109722754	12/2018	CN	N/A
110747523	12/2019	CN	N/A
1338349	12/1972	GB	N/A

Primary Examiner: Huson; Monica A

Attorney, Agent or Firm: Cooper Legal Group, LLC

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS

(1) This patent application claims the benefit and priority of Chinese Patent Application No. 202110691029.9 filed on Jun. 22, 2021, the disclosure of which is incorporated by reference herein in its entirety as part of the present application.

TECHNICAL FIELD

(2) The present disclosure relates to the technical field of electrostatic spinning, in particular to a

device and a method for twisting electrostatic spinning superfine fiber.

BACKGROUND ART

(3) The electrostatic spinning technology is a fiber manufacturing method in which a polymer solution or a melt forms a jet flow under the action of a strong electric field and the jet flow is solidified to form fiber. As a special fiber manufacturing process, polymer fiber with nanoscale diameter can be produced through an electrostatic spinning technology, and the electrostatic spinning technology is considered as one of superfine fiber preparation methods with the most industrial prospect.

(4) A non-woven fabric fiber felt is generally the product obtained by a traditional electrostatic spinning method, and the application range of the non-woven fabric fiber felt is limited. The fiber is bundled or twisted and collected, so that the tensile strength of the fiber can be improved, and ordered arrangement of the fiber can be promoted. The application potential of the electrostatic spinning method in the fields of spinning, sensors, tissue engineering and the like can be excited to a great extent.

(5) At present, electrostatic spinning superfine fiber twisting technology is mostly achieved by using rotating water flow or air flow to drive the fiber bundle to be bundled and twisted. The technology has the defects of poor stability and uniformity, and the twist degree cannot be accurately controlled. Electrostatic spinning needs high-voltage static electricity and protection such as electrostatic isolation, so that mechanical bundling and twisting are difficult.

SUMMARY

(6) The present disclosure aims to provide a device and a method for twisting electrostatic spinning superfine fiber so as to solve the problems in the prior art and improve the stability and the uniformity of electrostatic spinning fiber twisting.

(7) In order to achieve the purpose, the present disclosure provides the following scheme.

(8) The present disclosure provides a device for twisting electrostatic spinning superfine fiber, comprising an outer sleeve and a middle sleeve, wherein the outer sleeve sleeves the middle sleeve, an annular gap is formed between the outer sleeve and the middle sleeve, a melt inlet communicating with the annular gap is formed in the outer sleeve, a conical hole is formed in the bottom end of the outer sleeve, the top end of the conical hole communicates with the bottom end of the annular gap, and the outer sleeve is wrapped with a heating ring used for heating a melt in the annular gap; a cylindrical metal rod is arranged in the middle sleeve in a penetrating mode, an interval is formed between the metal rod and the middle sleeve, the bottom end of the metal rod is fixedly connected with a circular truncated cone located below the conical hole, the relatively large-area bottom surface of the circular truncated cone is fixedly connected with the bottom end of the metal rod, the relatively small-area bottom surface of the circular truncated cone is fixedly connected with a conical guide tip end, and the conical surface of the guide tip end is smoothly connected with the conical surface of the circular truncated cone; the metal rod, the circular truncated cone, the guide tip end and the annular gap are coaxial; and the device for twisting electrostatic spinning superfine fiber further comprises a roller below the guide tip end and a driving device capable of driving the metal rod to rotate, the metal rod is electrically connected with an output electrode of a high-voltage electrostatic generator, the circular truncated cone is conductive, the guide tip end is isolated, and the outer sleeve is grounded.

(9) Preferably, the device for twisting electrostatic spinning superfine fiber further comprises an inner sleeve, wherein the metal rod is inserted into the inner sleeve, the metal rod is fixedly connected with the inner sleeve, the inner sleeve is in running fit with the middle sleeve through a sliding bearing, and the inner sleeve and the sliding bearing are arranged in the interval; a rolling bearing is further fixedly arranged at the top end of the middle sleeve, an outer ring of the rolling bearing is fixedly connected with the middle sleeve, the rolling bearing sleeves the inner sleeve, and the inner sleeve is in transition fit with an inner ring of the rolling bearing.

(10) Preferably, an insulating shaft end sleeve is fixedly arranged at the top end of the metal rod,

the driving device is an adjustable-speed motor, and an output shaft of the adjustable-speed motor is fixedly connected with the insulating shaft end sleeve through a coupler.

(11) Preferably, a carbon brush support is fixedly arranged at the top end of the middle sleeve, the carbon brush support is connected with a carbon brush through a spring, the carbon brush support is further in threaded connection with a connecting screw, the connecting screw is electrically connected with an output electrode of the high-voltage electrostatic generator through a wire, the connecting screw is further fixedly connected with the end, away from the carbon brush, of the spring, and the carbon brush is in close contact with the side wall of the metal rod under the elastic force of the spring.

(12) Preferably, the bottom end of the conical hole is an annular tip end; and a plurality of jet flow guide balls are uniformly arranged at the bottom end of the conical hole.

(13) Preferably, the bottom end of the middle sleeve is further provided with a conical body coaxial with the metal rod corresponding to the conical hole, the conical body is located in the conical hole, an interval is formed between the conical surface of the conical body and the conical surface of the conical hole, the edge of the bottom end of the conical body extends out of the conical hole, the metal rod and the inner sleeve penetrate through the conical body, a gap is formed between the inner sleeve and the conical body, and the circular truncated cone is located below the conical body.

(14) Preferably, the taper of the guide tip end is the same as that of the circular truncated cone, and the size of the bottom surface of the guide tip end is the same as that of the cross section of the circular truncated cone.

(15) Preferably, the guide tip end is made of a high-temperature resistant insulating material such as polytetrafluoroethylene; and the circular truncated cone is made of graphite or metal.

(16) Preferably, a plurality of semicircular grooves are uniformly formed in the side surface of the circular truncated cone, and the length direction of the semicircular groove is the same as the inclination direction of the side surface.

(17) The present disclosure also provides a method for twisting electrostatic spinning superfine fiber based on the device for twisting electrostatic spinning superfine fiber, comprising the following steps: firstly, winding one end of a section of insulating string for a plurality of circles along the side surface of the circular truncated cone, bonding with the side surface of the circular truncated cone, winding the other end of the insulating string on the roller for a plurality of circles, and turning on the high-voltage electrostatic generator; secondly, after a polymer melt is melted and plasticized into a molten melt through an extruder, introducing the molten melt into the outer sleeve through the melt inlet, and meanwhile, opening the heating ring, wherein after flowing into the annular gap through the melt inlet, the molten melt continues to flow and is gradually and uniformly distributed in the circumferential direction, and then the molten melt continues to flow downwards to the inner side of the conical surface of the conical hole in the bottom of the outer sleeve; and the molten melt naturally flows downwards to the annular tip end at the bottom end of the outer sleeve along the inner wall surface due to the gravity effect and the adhesion effect and is annularly and uniformly distributed; thirdly, due to the fact that the circular truncated cone is electrified after the high-voltage electrostatic generator is started, forming a high-voltage electric field between the surface of the circular truncated cone and the annular tip end at the bottom end of the outer sleeve so that the annular tip end at the bottom end of the outer sleeve is electrified in an induction mode, and adjusting the output voltage of the high-voltage electrostatic generator until the melt thin layer attached to the annular tip end is excited to form multiple jet flows under the action of the high-voltage electric field, wherein the multiple jet flows are self-organized and gradually and uniformly distributed to form multiple jet flows which are uniformly and stably spaced, the jet flows are cooled and solidified to form continuous superfine fiber, and due to the electrostatic adsorption effect, the continuous superfine fiber is adsorbed to the insulating string wound on the side surface of the circular truncated cone; fourthly, turning on a rotary switch of the roller to enable the roller to rotate, winding the insulating string on the rotating roller so as to pull

and wind the superfine fiber on the roller, continuously and automatically winding the bundled fiber on the roller due to the fact that the spun fiber is continuous long fiber, turning on the adjustable-speed motor to drive the circular truncated cone to rotate, twisting a fiber bundle adsorbed on the conical surface of the bottom of the circular truncated cone, and continuously collecting yarn formed after twisting by the roller; and fifthly, adjusting the yarn twist by adjusting the rotating speed of the adjustable-speed motor so that the yarn meets the technological requirements, and changing the quantity of jet flows formed by exciting the melt thin layer attached to the annular tip end by changing the output voltage of the high-voltage electrostatic generator so that the technological requirement of the quantity of fiber in the yarn is met.

(18) Compared with the prior art, the present disclosure has the following technical effects.

(19) According to the device and the method for twisting electrostatic spinning superfine fiber, the stability and the uniformity of electrostatic spinning fiber twisting are improved. According to the device and the method for twisting electrostatic spinning superfine fiber, multiple fibers generated at the annular tip end are adsorbed to the circular truncated cone through the electrostatic adsorption effect of the circular truncated cone, so that the purpose of bundling is achieved. Then, the fiber bundle is twisted through the rotation effect of the circular truncated cone, and finally twisted yarn is received by the roller and collected in a rolled mode. The device has the functions of bundling, twisting and collecting the superfine fiber prepared by the electrostatic spinning method, and has the advantages of high stability, high continuity, twist adjustability and the like.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) To more clearly illustrate the embodiment of the present disclosure or the technical scheme in the prior art, the following briefly introduces the attached figures to be used in the embodiment. Apparently, the attached figures in the following description show merely some embodiments of the present disclosure, and those skilled in the art may still derive other drawings from these attached figures without creative efforts.

(2) FIG. 1 is a structural schematic diagram of a device for twisting electrostatic spinning superfine fiber in the first embodiment of the present disclosure;

(3) FIG. 2 is a partial structural schematic diagram I of a device for twisting electrostatic spinning superfine fiber in the first embodiment of the present disclosure;

(4) FIG. 3 is a partial structural schematic diagram II of a device for twisting electrostatic spinning superfine fiber in the first embodiment of the present disclosure;

(5) FIG. 4 is a partial structural schematic diagram of a device for twisting electrostatic spinning superfine fiber in the second embodiment of the present disclosure;

(6) FIG. 5 is a partial structural schematic diagram of a device for twisting electrostatic spinning superfine fiber in the third embodiment of the present disclosure;

(7) FIG. 6 is a partial structural schematic diagram III of a device for twisting electrostatic spinning superfine fiber in the first embodiment of the present disclosure;

(8) FIG. 7 is a partial structural schematic diagram of a device for twisting electrostatic spinning superfine fiber in the fourth embodiment of the present disclosure; and

(9) FIG. 8 is a structural schematic diagram of a device for twisting electrostatic spinning superfine fiber in the fifth embodiment of the present disclosure.

(10) Reference signs: **100**, device for twisting electrostatic spinning superfine fiber; **1**, outer sleeve; **2**, middle sleeve; **3**, annular gap; **4**, sliding bearing; **5**, inner sleeve; **6**, metal rod; **7**, circular truncated cone; **8**, guide tip end; **9**, melt inlet; **10**, roller; **11**, speed-adjustable motor; **12**, output shaft; **13**, coupler; **14**, insulating shaft end sleeve; **15**, set screw; **16**, high-voltage electrostatic generator; **17**, wire; **18**, carbon brush support; **19**, connecting screw; **20**, spring; **21**, carbon brush;

22, rolling bearing; 23, heating ring; 24, fiber; 25, yarn; 26, hemispherical body; 27, jet flow guide ball; 28, semicircular groove; 29, conical body; and 30, bolt.

DETAILED DESCRIPTION OF THE EMBODIMENTS

(11) The following clearly and completely describes the technical scheme in the embodiments of the present disclosure with reference to the attached figures in the embodiments of the present disclosure. Apparently, the described embodiments are merely a part rather than all of the embodiments of the present disclosure. Based on the embodiment in the present disclosure, all other embodiments obtained by the ordinary technical staff in the art under the premise of without contributing creative labor belong to the scope protected by the present disclosure.

(12) The present disclosure aims to provide a device and a method for twisting electrostatic spinning superfine fiber so as to solve the problems in the prior art and improve the stability and the uniformity of electrostatic spinning fiber twisting.

(13) To make the foregoing objective, features and advantages of the present disclosure clearer and more comprehensible, the present disclosure is further described in detail below with reference to the attached figures and specific embodiments.

Embodiment I

(14) As shown in FIG. 1 to FIG. 3 and FIG. 3, the embodiment provides a device **100** for twisting electrostatic spinning superfine fiber, comprising an outer sleeve **1** and a middle sleeve **2**, wherein the outer sleeve **1** sleeves the middle sleeve **2**, an annular gap **3** is formed between the outer sleeve **1** and the middle sleeve **2**, a melt inlet **9** communicating with the annular gap **3** is formed in the outer sleeve **1**, a conical hole is formed in the bottom end of the outer sleeve **1**, the top end of the conical hole communicates with the bottom end of the annular gap **3**, and the bottom end of the conical hole is an annular tip end; the outer sleeve **1** is wrapped with a heating ring **23** used for heating a melt in the annular gap **3**; a cylindrical metal rod **6** is arranged in the middle sleeve **2** in a penetrating mode, an interval is formed between the metal rod **6** and the middle sleeve **2**, the bottom end of the metal rod **6** is fixedly connected with a circular truncated cone **7** located below the conical hole, the relatively large-area bottom surface of the circular truncated cone **7** is fixedly connected with the bottom end of the metal rod **6**, the relatively small-area bottom surface of the circular truncated cone **7** is fixedly connected with a conical guide tip end **8**, and the conical surface of the guide tip end **8** is smoothly connected with the conical surface of the circular truncated cone **7**; the metal rod **6**, the circular truncated cone **7**, the guide tip end **8** and the annular gap **3** are coaxial and all vertical; and the taper of the guide tip end **8** is the same as that of the circular truncated cone **7**, and the size of the bottom surface of the guide tip end **8** is the same as that of the cross section of the circular truncated cone **7**. The guiding tip end **8** is made of a high-temperature resistant insulating material such as polytetrafluoroethylene, so that spinning process interruption caused by self protection of the high-voltage electrostatic generator **16** due to electric conduction of the circular truncated cone **7** and the middle sleeve **2** is prevented; and the circular truncated cone **7** is made of a conductive material such as graphite or metal. In the embodiment, the circular truncated cone **7** at the bottom end of the metal rod **6** serves as a high-voltage electrode, the guiding tip end **8** is used for guiding the collecting direction of yarn **25**. Meanwhile, the situation that the twisting turning radius is insufficient due to the fact that fiber **24** is attracted by the tip end is avoided, and the twisting effect is guaranteed.

(15) In the embodiment, the device **100** for twisting electrostatic spinning superfine fiber further comprises an inner sleeve **5**, wherein the metal rod **6** is inserted into the inner sleeve **5**, the metal rod **6** is fixedly connected with the inner sleeve **5**, the inner sleeve **5** is in running fit with the middle sleeve **2** through a sliding bearing **4**, and the inner sleeve **5** and the sliding bearing **4** are arranged in the interval between the metal rod **6** and the middle sleeve **2**; a rolling bearing **22** is further fixedly arranged at the top end of the middle sleeve **2**, an outer ring of the rolling bearing **22** is fixedly connected with the middle sleeve **2**, the rolling bearing **22** sleeves the inner sleeve **5**, and the inner sleeve **5** is in transition fit with an inner ring of the rolling bearing **22**. The extending

distance of the conical surface high-voltage electrode at the bottom of the spinning nozzle outer sleeve **1** can be adjusted by sliding the inner sleeve **5** up and down relative to the rolling bearing **22**.

(16) In the embodiment, the device **100** for twisting electrostatic spinning superfine fiber further comprises a roller **10** below the guide tip end **8** and a speed-adjustable motor **11** capable of driving the metal rod **6** to rotate. The roller **10** can rotate and is adjustable in rotating speed. The roller **10** and a driving device thereof are common equipment in the spinning field, and the specific structures thereof will not be described in detail herein.

(17) The metal rod **6** is electrically connected with an output electrode of a high-voltage electrostatic generator **16**, the circular truncated cone **7** is conductive, the guide tip end **8** is isolated, and the outer sleeve **1** is grounded. An insulating shaft end sleeve **14** is fixedly arranged at the top end of the metal rod **6**. A set screw **15** is arranged on the insulating shaft end sleeve **14**, and the circumferential fixation of the insulating shaft end sleeve **14** and the metal rod **6** is realized through the set screw **15**. An output shaft **12** of the adjustable-speed motor **11** is fixedly connected with the insulating shaft end sleeve **14** through a coupler **13**. A carbon brush support **18** is fixedly arranged at the top end of the middle sleeve **2**, the carbon brush support **18** is fixedly mounted on the middle sleeve **2**, the carbon brush support **18** is connected with a carbon brush **21** through a spring **20**, the carbon brush support **18** is further in threaded connection with a connecting screw **19**, the connecting screw **19** is electrically connected with an output electrode of the high-voltage electrostatic generator **16** through a wire **17**, the connecting screw **19** is further fixedly connected with the end, away from the carbon brush **21**, of the spring **20**, and the carbon brush **21** is in close contact with the side wall of the metal rod **6** under the elastic force of the spring **20**. The tightness of the spring **20** can be adjusted by adjusting the screwing depth of the connecting screw **19**.

(18) The present disclosure also provides a method for twisting electrostatic spinning superfine fiber **24** based on the device **100** for twisting electrostatic spinning superfine fiber, comprising the following steps: firstly, winding one end of a section of insulating string for a plurality of circles along the side surface of the circular truncated cone **7**, slightly bonding with the side surface of the circular truncated cone **7** in order to ensure that the insulating string can be separated from the circular truncated cone **7** when the roller **10** drives the insulating string to rotate on the basis that the insulating string can rotate along with the circular truncated cone **7**, winding the other end of the insulating string on the roller **10** for a plurality of circles, and turning on the high-voltage electrostatic generator **16**; secondly, after a polymer melt is melted and plasticized into a molten melt through an extruder, introducing the molten melt into the outer sleeve **1** through the melt inlet **9**, and meanwhile, opening the heating ring **23**, wherein after flowing into the annular gap **3** through the melt inlet **9**, the molten melt continues to flow and is gradually and uniformly distributed in the circumferential direction, and then the molten melt continues to flow downwards to the inner side of the conical surface of the conical hole in the bottom of the outer sleeve **1**; the molten melt naturally flows downwards to the annular tip end at the bottom end of the outer sleeve **1** along the inner wall surface due to the gravity effect and the adhesion effect and is annularly and uniformly distributed; and the heating ring **23** is used for maintaining the temperature of the melt so as to maintain the flowability of the melt; thirdly, due to the fact that the circular truncated cone **7** is electrified after the high-voltage electrostatic generator **16** is started, forming a high-voltage electric field between the surface of the circular truncated cone **7** and the annular tip end at the bottom end of the outer sleeve **1** so that the annular tip end at the bottom end of the outer sleeve **1** is electrified in an induction mode, and adjusting the output voltage of the high-voltage electrostatic generator **16** until the melt thin layer attached to the annular tip end is excited to form multiple jet flows under the action of the high-voltage electric field, wherein the multiple jet flows are self-organized and gradually and uniformly distributed to form multiple jet flows which are uniformly and stably spaced, the jet flows are cooled and solidified to form continuous superfine fiber **24**, and due to the electrostatic adsorption effect, the continuous superfine fiber **24** is adsorbed

to the insulating string wound on the side surface of the circular truncated cone **7**; fourthly, turning on a rotary switch of the roller **10** to enable the roller **10** to rotate, winding the insulating string on the rotating roller **10** so as to pull and wind the superfine fiber **24** on the roller **10**, continuously and automatically winding the bundled fiber **24** on the roller **10** due to the fact that the spun fiber **24** is continuous long fiber **24**, turning on the adjustable-speed motor **11** to drive the circular truncated cone **7** to rotate, twisting a fiber **24** bundle adsorbed on the conical surface of the bottom of the circular truncated cone **7**, and continuously collecting yarn **25** formed after twisting by the roller; and fifthly, adjusting the yarn **25** twist by adjusting the rotating speed of the adjustable-speed motor **11** so that the yarn **25** meets the technological requirements, and changing the quantity of jet flows formed by exciting the melt thin layer attached to the annular tip end by changing the output voltage of the high-voltage electrostatic generator **16** so that the technological requirement of the quantity of fiber **24** in the yarn **25** is met; and adjusting the twisting frictional force by changing the roughness of the side surface of the circular truncated cone.

Embodiment II

(19) The device **100** for twisting electrostatic spinning superfine fiber provided by the embodiment is basically the same as the device **100** for twisting electrostatic spinning superfine fiber provided by the first embodiment in general structure, and the difference is only that, as shown in FIG. **4**, the bottom end of the metal rod **6** in the device **100** for twisting electrostatic spinning superfine fiber is not provided with a circular truncated cone **7** or a guide tip end **8**; however, a hemispherical body **26** is fixedly arranged as a high-voltage electrode, the spherical surface of the hemispherical body **26** faces downwards, the circular bottom surface of the hemispherical body **26** is fixedly connected with the bottom end of the metal rod **6**, and the hemispherical body **26** and the metal rod **6** are coaxial.

Embodiment III

(20) The device **100** for twisting electrostatic spinning superfine fiber provided by the embodiment is basically the same as the device **100** for twisting electrostatic spinning superfine fiber provided by the first embodiment in general structure, and the difference is only that, as shown in FIG. **5**, a plurality of jet flow guide balls **27** are uniformly arranged at the bottom end of the conical hole in the bottom end of the outer sleeve **1**, and an interval exists between every two adjacent jet flow guide balls **27**. The jet flow guide balls **27** arranged in the embodiment are used for guiding the quantity of fixed fiber **24** to meet the specific process requirement.

(21) Specifically, after flowing to the annular tip end along the inner conical surface of the conical hole in the bottom of the outer sleeve **1**, the polymer melt is uniformly distributed on the annular tip end and the surface of the jet flow guide ball **27**. The bottom tip end of the jet flow guide ball **27** protrudes out of the annular tip end. Therefore, due to the tip end discharge effect, the charge of the bottom tip end of the jet flow guide ball **27** is the most dense, a the field intensity of the bottom tip end of the jet flow guide ball **27** is the strongest, and a jet flow can be excited and formed. The melt also continuously flows to the surface of the jet flow guide ball to form the stable jet flow.

Specifically, after the high-voltage electrostatic generator **16** is turned on, due to the tip end discharge effect, the induction field intensity near the bottom tip end of the jet flow guide ball **27** is the strongest. The melt attached to the bottom surface of the jet flow guide ball **27** is excited to form the jet flow. More melts on the surfaces of the jet flow guide balls **27** are taken away along with continuous operation of the jet flow. At the moment, more melts need to be supplemented to the surfaces of the jet flow guide balls **27**, so that the melts on the surface of the inner conical surface are guided to be continuously supplemented to the surfaces of the jet flow guide balls **27**. Due to the tip end discharge effect of the jet flow guide ball **27**, the induction field intensity of the bottom tip end of the jet flow guide ball **27** is the strongest, jet flow is only generated at the bottom tip end of the jet flow guide ball **27**, and the function of guiding the jet flow is achieved. Therefore, the quantity of the jet flows depends on the quantity of the jet flow guide balls **27**, and the quantity of the finally formed jet flows can be controlled by changing the quantity of the jet flow guide balls

27.

Embodiment IV

(22) The device **100** for twisting electrostatic spinning superfine fiber provided by the embodiment is basically the same as the device **100** for twisting electrostatic spinning superfine fiber provided by the first embodiment in general structure, and the difference is only that, as shown in FIG. 7, a plurality of semicircular grooves **28** are uniformly formed in the side surface of the circular truncated cone **7**, and the length direction of the semicircular groove **28** is the same as the inclination direction of the side surface. The semicircular grooves **28** can be only distributed in the side surface of the circular truncated cone **7** and can also extend downwards to the conical surface of the guide tip end **8**, and the semicircular grooves **28** can enhance the twisting effect of the circular truncated cone **7** on the high-voltage electrode of the superfine fiber.

Embodiment V

(23) The device **100** for twisting electrostatic spinning superfine fiber provided by the embodiment is basically the same as the device **100** for twisting electrostatic spinning superfine fiber provided by the first embodiment in general structure, and the difference is only that, as shown in FIG. 8, the bottom end of the middle sleeve **2** is further provided with a conical body **29** coaxial with the metal rod **6** corresponding to the conical hole, the conical body **29** is located in the conical hole, an interval is formed between the conical surface of the conical body **29** and the conical surface of the conical hole, the edge of the bottom end of the conical body **29** extends out of the conical hole, the metal rod **6** and the inner sleeve **5** penetrate through the conical body **29**, a gap is formed between the inner sleeve **5** and the conical body **29**, and the circular truncated cone **7** is located below the conical body **29**. In the embodiment, a molten fluid in the annular gap **3** can flow to the bottom edge of the conical body **29**, the melt thin layer is formed at the bottom edge of the conical body **29** and is excited into the jet flow to be spun and twisted.

(24) In the description of the present disclosure, it needs to be illustrated that the indicative direction or position relations of the terms such as “center”, “top”, “bottom”, “left”, “right”, “vertical”, “horizontal”, “inside” and “outside” are direction or position relations illustrated based on the attached figures, just for facilitating the description of the present disclosure and simplifying the description, but not for indicating or hinting that the indicated device or element must be in a specific direction and is constructed and operated in the specific direction, the terms cannot be understood as the restriction of the present disclosure.

(25) Specific examples are used for illustration of the principles and implementation methods of the present disclosure. The description of the above-mentioned embodiments is used to help illustrate the method and the core principles of the present disclosure; and meanwhile, those skilled in the art can make various modifications in terms of specific embodiments and scope of application in accordance with the teachings of the present disclosure. In conclusion, the content of this specification shall not be construed as a limitation to the present disclosure.

Claims

1. A device for twisting electrostatic spinning superfine fiber, comprising: an outer sleeve and a middle sleeve, wherein the outer sleeve sleeves the middle sleeve, an annular gap is formed between the outer sleeve and the middle sleeve, a melt inlet communicating with the annular gap is formed in the outer sleeve, a conical hole is formed in the bottom end of the outer sleeve, the top end of the conical hole communicates with the bottom end of the annular gap, and the outer sleeve is wrapped with a heating ring used for heating a melt in the annular gap; a cylindrical metal rod, wherein the cylindrical metal rod is arranged in the middle sleeve in a penetrating mode, an interval is formed between the metal rod and the middle sleeve, the bottom end of the metal rod is fixedly connected with a circular truncated cone located below the conical hole, a relatively large-area bottom surface of the circular truncated cone is fixedly connected with the bottom end of the metal

rod, the relatively small-area bottom surface of the circular truncated cone is fixedly connected with a conical guide tip end, and the conical surface of the guide tip end is smoothly connected with the conical surface of the circular truncated cone; wherein the metal rod, the circular truncated cone, the guide tip end and the annular gap are coaxial; a roller below the guide tip end; and a driving device capable of driving the metal rod to rotate, wherein the metal rod is electrically connected with an output electrode of a high-voltage electrostatic generator, the circular truncated cone is conductive, the guide tip end is isolated, and the outer sleeve is grounded.

2. The device for twisting electrostatic spinning superfine fiber according to claim 1, further comprising: an inner sleeve, wherein the metal rod is inserted into the inner sleeve, the metal rod is fixedly connected with the inner sleeve, the inner sleeve is in running fit with the middle sleeve through a sliding bearing, and the inner sleeve and the sliding bearing are arranged in the interval; and a rolling bearing, wherein the rolling bearing is further fixedly arranged at the top end of the middle sleeve, an outer ring of the rolling bearing is fixedly connected with the middle sleeve, the rolling bearing sleeves the inner sleeve, and the inner sleeve is in transition fit with an inner ring of the rolling bearing.

3. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein an insulating shaft end sleeve is fixedly arranged at the top end of the metal rod, the driving device is an adjustable-speed motor, and an output shaft of the adjustable-speed motor is fixedly connected with the insulating shaft end sleeve through a coupler.

4. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein a carbon brush support is fixedly arranged at the top end of the middle sleeve, the carbon brush support is connected with a carbon brush through a spring, the carbon brush support is further in threaded connection with a connecting screw, the connecting screw is electrically connected with an output electrode of the high-voltage electrostatic generator through a wire, the connecting screw is further fixedly connected with the end away from the carbon brush of the spring, and the carbon brush is in close contact with the side wall of the metal rod under the elastic force of the spring.

5. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein the bottom end of the conical hole is an annular tip end; and a plurality of jet flow guide balls are uniformly arranged at the bottom end of the conical hole.

6. The device for twisting electrostatic spinning superfine fiber according to claim 2, wherein the bottom end of the middle sleeve is further provided with a conical body coaxial with the metal rod corresponding to the conical hole, the conical body is located in the conical hole, an interval is formed between the conical surface of the conical body and the conical surface of the conical hole, the edge of the bottom end of the conical body extends out of the conical hole, the metal rod and the inner sleeve penetrate through the conical body, a gap is formed between the inner sleeve and the conical body, and the circular truncated cone is located below the conical body.

7. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein a taper of the guide tip end is the same as that of the circular truncated cone, and the size of the bottom surface of the guide tip end is the same as that of the cross section of the circular truncated cone.

8. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein the guide tip end is made of a high-temperature resistant insulating material; and the circular truncated cone is made of graphite or metal.

9. The device for twisting electrostatic spinning superfine fiber according to claim 1, wherein a plurality of semicircular grooves are uniformly formed in the side surface of the circular truncated cone, and the length direction of the semicircular groove is the same as the inclination direction of the side surface.

10. A method for twisting electrostatic spinning superfine fiber, based on the device for twisting electrostatic spinning superfine fiber according to claim 1, comprising the following steps: winding one end of a section of insulating string for a plurality of circles along the side surface of the

circular truncated cone, bonding with the side surface of the circular truncated cone, winding the other end of the insulating string on the roller for a plurality of circles, and turning on the high-voltage electrostatic generator; after a polymer melt is melted and plasticized into a molten melt through an extruder, introducing the molten melt into the outer sleeve through the melt inlet, and meanwhile, opening the heating ring, wherein after flowing into the annular gap through the melt inlet, the molten melt continues to flow and is gradually and uniformly distributed in the circumferential direction, and then the molten melt continues to flow downwards to the inner side of the conical surface of the conical hole in the bottom of the outer sleeve; and the molten melt naturally flows downwards to the annular tip end at the bottom end of the outer sleeve along the inner wall surface due to the gravity effect and the adhesion effect and is annularly and uniformly distributed; due to the fact that the circular truncated cone is electrified after the high-voltage electrostatic generator is started, forming a high-voltage electric field between the surface of the circular truncated cone and the annular tip end at the bottom end of the outer sleeve so that the annular tip end at the bottom end of the outer sleeve is electrified in an induction mode, and adjusting the output voltage of the high-voltage electrostatic generator until the melt thin layer attached to the annular tip end is excited to form multiple jet flows under the action of the high-voltage electric field, wherein the multiple jet flows are self-organized and gradually and uniformly distributed to form multiple jet flows which are uniformly and stably spaced, the jet flows are cooled and solidified to form continuous superfine fiber, and due to the electrostatic adsorption effect, the continuous superfine fiber is adsorbed to the insulating string wound on the side surface of the circular truncated cone; turning on a rotary switch of the roller to enable the roller to rotate, winding the insulating string on the rotating roller so as to pull and wind the superfine fiber on the roller, continuously and automatically winding the bundled fiber on the roller due to the fact that the spun fiber is continuous long fiber, turning on an adjustable-speed motor to drive the circular truncated cone to rotate, twisting the fiber bundle adsorbed on the conical surface of the bottom of the circular truncated cone, and continuously collecting yarn formed after twisting by the roller; and adjusting the yarn twist by adjusting the rotating speed of the adjustable-speed motor so that the yarn meets the technological requirements, and changing the quantity of jet flows formed by exciting the melt thin layer attached to the annular tip end by changing the output voltage of the high-voltage electrostatic generator so that the technological requirement of the quantity of fiber in the yarn is met.

11. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein the device comprises: an inner sleeve, wherein the metal rod is inserted into the inner sleeve, the metal rod is fixedly connected with the inner sleeve, the inner sleeve is in running fit with the middle sleeve through a sliding bearing, and the inner sleeve and the sliding bearing are arranged in the interval; and a rolling bearing, wherein the rolling bearing is further fixedly arranged at the top end of the middle sleeve, an outer ring of the rolling bearing is fixedly connected with the middle sleeve, the rolling bearing sleeves the inner sleeve, and the inner sleeve is in transition fit with an inner ring of the rolling bearing.

12. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein an insulating shaft end sleeve is fixedly arranged at the top end of the metal rod, the driving device is an adjustable-speed motor, and an output shaft of the adjustable-speed motor is fixedly connected with the insulating shaft end sleeve through a coupler.

13. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein a carbon brush support is fixedly arranged at the top end of the middle sleeve, the carbon brush support is connected with a carbon brush through a spring, the carbon brush support is further in threaded connection with a connecting screw, the connecting screw is electrically connected with an output electrode of the high-voltage electrostatic generator through a wire, the connecting screw is further fixedly connected with the end away from the carbon brush of the spring, and the carbon brush is in close contact with the side wall of the metal rod under the elastic force of the spring.

14. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein the bottom end of the conical hole is an annular tip end; and a plurality of jet flow guide balls are uniformly arranged at the bottom end of the conical hole.

15. The method for twisting electrostatic spinning superfine fiber according to claim 11, wherein the bottom end of the middle sleeve is further provided with a conical body coaxial with the metal rod corresponding to the conical hole, the conical body is located in the conical hole, an interval is formed between the conical surface of the conical body and the conical surface of the conical hole, the edge of the bottom end of the conical body extends out of the conical hole, the metal rod and the inner sleeve penetrate through the conical body, a gap is formed between the inner sleeve and the conical body, and the circular truncated cone is located below the conical body.

16. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein a taper of the guide tip end is the same as that of the circular truncated cone, and the size of the bottom surface of the guide tip end is the same as that of the cross section of the circular truncated cone.

17. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein the guide tip end is made of a high-temperature resistant insulating material; and the circular truncated cone is made of graphite or metal.

18. The method for twisting electrostatic spinning superfine fiber according to claim 10, wherein a plurality of semicircular grooves are uniformly formed in the side surface of the circular truncated cone, and the length direction of the semicircular groove is the same as the inclination direction of the side surface.

19. A method for twisting electrostatic spinning superfine fiber comprising the following steps: winding one end of a section of insulating string for a plurality of circles along the side surface of a circular truncated cone, bonding with a side surface of the circular truncated cone, winding the other end of the insulating string on a roller for a plurality of circles, and turning on a high-voltage electrostatic generator; after a polymer melt is melted and plasticized into a molten melt through an extruder, introducing the molten melt into an outer sleeve through a melt inlet, and meanwhile, opening a heating ring, wherein after flowing into an annular gap through the melt inlet, the molten melt continues to flow and is gradually and uniformly distributed in the circumferential direction, and then the molten melt continues to flow downwards to the inner side of the conical surface of a conical hole in the bottom of an outer sleeve; and the molten melt naturally flows downwards to an annular tip end at the bottom end of the outer sleeve along the inner wall surface due to the gravity effect and the adhesion effect and is annularly and uniformly distributed; due to the fact that the circular truncated cone is electrified after the high-voltage electrostatic generator is started, forming a high-voltage electric field between the surface of the circular truncated cone and the annular tip end at the bottom end of the outer sleeve so that the annular tip end at the bottom end of the outer sleeve is electrified in an induction mode, and adjusting the output voltage of the high-voltage electrostatic generator until the melt thin layer attached to the annular tip end is excited to form multiple jet flows under the action of the high-voltage electric field, wherein the multiple jet flows are self-organized and gradually and uniformly distributed to form multiple jet flows which are uniformly and stably spaced, the jet flows are cooled and solidified to form continuous superfine fiber, and due to the electrostatic adsorption effect, the continuous superfine fiber is adsorbed to the insulating string wound on the side surface of the circular truncated cone; turning on a rotary switch of the roller to enable the roller to rotate, winding the insulating string on the rotating roller so as to pull and wind the superfine fiber on the roller, continuously and automatically winding the bundled fiber on the roller due to the fact that the spun fiber is continuous long fiber, turning on an adjustable-speed motor to drive the circular truncated cone to rotate, twisting the fiber bundle adsorbed on the conical surface of the bottom of the circular truncated cone, and continuously collecting yarn formed after twisting by the roller; and adjusting the yarn twist by adjusting the rotating speed of the adjustable-speed motor so that the yarn meets the technological requirements,

and changing the quantity of jet flows formed by exciting the melt thin layer attached to the annular tip end by changing the output voltage of the high-voltage electrostatic generator so that the technological requirement of the quantity of fiber in the yarn is met.
