

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408348
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Kang; Byung Woo

Semiconductor device and manufacturing method thereof

Abstract

A semiconductor device and a method of manufacturing the semiconductor includes a first source layer spaced apart from a substrate and disposed in a memory cell region of the substrate, a second source layer spaced apart from the substrate and disposed in a contact region of the substrate, a cell stacked structure including interlayer insulating layers and conductive patterns alternately stacked on each other over the first source layer, a discharge contact passing through at least a part of the second source layer, and a dielectric layer disposed between the second source layer and the discharge contact.

Inventors:	Kang; Byung Woo (Icheon-si, KR)
Applicant:	SK hynix Inc. (Icheon-si, KR)
Family ID:	86991415
Assignee:	SK hynix Inc. (Icheon-si, KR)
Appl. No.:	17/837788
Filed:	June 10, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230217662 A1	Jul. 06, 2023

Foreign Application Priority Data

KR	10-2022-0000606	Jan. 03, 2022
----	-----------------	---------------

Publication Classification

Int. Cl.: H10B53/20 (20230101)

U.S. Cl.:

CPC **H10B53/20** (20230201);

Field of Classification Search

CPC: H10B (53/20); H10B (43/35); H10B (43/27); H10B (43/40); G11C (16/0483); H01L (28/60)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2020/0381447	12/2019	Kim	N/A	H10B 43/27

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1020200113871	12/2019	KR	N/A
1020200137699	12/2019	KR	N/A
1020210011789	12/2020	KR	N/A

Primary Examiner: Hanley; Britt D

Assistant Examiner: Trice, III; William C.

Attorney, Agent or Firm: WILLIAM PARK & ASSOCIATES LTD.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) The present application claims priority under 35 U.S.C. § 119(a) to Korean patent application number 10-2022-0000606, filed on Jan. 3, 2022, in the Korean Intellectual Property Office, the entire disclosure of which is incorporated herein by reference.

BACKGROUND

1. Technical Field

(2) Various embodiments of the present disclosure generally relate to an electronic device, and more particularly, to a semiconductor device and a manufacturing method of the semiconductor device.

2. Related Art

(3) Non-volatile memory devices retain stored data even in the absence of supplied power. The increase in integration density of two-dimensional non-volatile memory devices in which memory cells are formed in a single layer over a substrate has recently been limited. Thus, three-dimensional non-volatile memory devices have been proposed in which memory cells are stacked in a vertical direction over a substrate.

(4) Three-dimensional non-volatile memory devices may include interlayer insulating layers and gate electrodes alternately stacked on each other and channel layers passing through the interlayer insulating layers and the gate electrodes, and memory cells may be stacked along the channel layers. Various structures and manufacturing methods have been developed to improve the

operational reliability of three-dimensional non-volatile memory devices.

SUMMARY

(5) According to an embodiment of the present disclosure, a semiconductor device may include a first source layer spaced apart from a substrate and disposed in a memory cell region of the substrate, a second source layer spaced apart from the substrate and disposed in a contact region of the substrate, a cell stacked structure including interlayer insulating layers and conductive patterns alternately stacked on each other over the first source layer, a discharge contact passing through at least a part of the second source layer, and a dielectric layer disposed between the second source layer and the discharge contact.

(6) According to an embodiment of the present disclosure, a semiconductor device may include a source layer spaced apart from a substrate and disposed in a memory cell region and a contact region of the substrate, a cell stacked structure including interlayer insulating layers and conductive patterns alternately stacked on each other over the source layer in the memory cell region, a channel structure passing through at least a part of the cell stacked structure and extending into the source layer in the memory cell region, an electrode for a capacitor passing through at least a part of the source layer in the contact region, and a dielectric layer disposed between the source layer and the electrode for the capacitor.

(7) According to an embodiment of the present disclosure, a method of manufacturing a semiconductor device may include forming a source layer over a substrate including a memory cell region and a contact region, forming a contact hole passing through the source layer in the contact region, forming a dielectric layer on a sidewall of the contact hole, filling the contact hole with a conductive material, forming a stacked structure in which first material layers and second material layers are alternately stacked on each other over the source layer and the conductive material, and forming a plurality of channel holes passing through the stacked structure to extend into the source layer.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a block diagram illustrating a semiconductor device according to an embodiment;

(2) FIG. 2 is a cross-sectional diagram illustrating a semiconductor device according to an embodiment;

(3) FIG. 3 is an enlarged cross-sectional diagram of a capacitor shown in FIG. 2;

(4) FIGS. 4A to 4G are diagrams illustrating a method of manufacturing a semiconductor device according to an embodiment;

(5) FIGS. 5A to 5C are layout views illustrating various embodiments of a discharge contact;

(6) FIG. 6 is a block diagram illustrating a configuration of a memory system according to an embodiment;

(7) FIG. 7 is a block diagram illustrating a configuration of a memory system according to an embodiment;

(8) FIG. 8 is a block diagram illustrating a configuration of a computing system according to an embodiment; and

(9) FIG. 9 is a block diagram illustrating a computing system according to an embodiment.

DETAILED DESCRIPTION

(10) Specific structural or functional descriptions disclosed herein are merely illustrative for the purpose of describing embodiments according to the concept of the present disclosure.

Embodiments according to the concept of the present disclosure may be implemented in various forms and should not be construed as being limited to the specific embodiments set forth herein.

(11) Hereinafter, embodiments are described with reference to the accompanying drawings in order

for those skilled in the art to be able to implement the technical spirit of the present disclosure.

(12) Various embodiments are directed to a semiconductor device capable of utilizing, as a capacitor, a discharge contact for discharging charges accumulated in a source layer of the semiconductor device and a method of manufacturing the semiconductor device.

(13) FIG. 1 is a block diagram illustrating a semiconductor device according to an embodiment.

(14) Referring to FIG. 1, the semiconductor device may include a peripheral circuit structure PC and memory blocks BLK1 to BLKk that are disposed over a substrate SUB, where k is a natural number of 2 or more. The memory blocks BLK1 to BLKk may overlap the peripheral circuit structure PC.

(15) The substrate SUB may be a single crystal semiconductor layer. For example, the substrate SUB may be a bulk silicon substrate, a silicon-on-insulator substrate, a germanium substrate, a germanium-on-insulator substrate, a silicon-germanium substrate, or an epitaxial thin film formed by a selective epitaxial growth method.

(16) The peripheral circuit structure PC may include a row decoder, a column decoder, a page buffer, and a control circuit that form a circuit for controlling the operation of the memory blocks BLK1 to BLKk. For example, the peripheral circuit structure PC may include an NMOS transistor, a PMOS transistor, a resistor, and a capacitor that are electrically coupled to the memory blocks BLK1 to BLKk. The peripheral circuit structure PC may be disposed between the substrate SUB and the memory blocks BLK1 to BLKk. However, the present disclosure does not exclude an embodiment in which the peripheral circuit structure PC extends to a region of the substrate SUB which does not overlap with the memory blocks BLK1 and BLKk.

(17) Each of the memory blocks BLK1 to BLKk may include impurity-doped regions, bit lines, cell strings electrically coupled to the impurity-doped regions and the bit lines, word lines electrically coupled to the cell strings, and select lines electrically coupled to the cell strings. Each of the cell strings may include memory cells and select transistors that are coupled in series to each other by a channel structure. Each of the select lines may serve as a gate electrode of a corresponding one of the select transistors. Each of the word lines may serve as a gate electrode of a corresponding one of the memory cells.

(18) FIG. 2 is a cross-sectional diagram illustrating a semiconductor device according to an embodiment.

(19) Referring to FIG. 2, the semiconductor device may include source layers SLa and SLb disposed over the substrate SUB, a cell stacked structure STc disposed over the source layer SLa, a dummy stacked structure STd disposed over the source layer SLb, and a discharge contact DCC passing through a region of the source layer SLb that overlaps the dummy stacked structure STd and extending downwards. For example, a region of the substrate SUB in which the source layer SLa and the cell stacked structure STc are formed may be defined as a memory cell region and a region of the substrate SUB in which the source layer SLb, the dummy stacked structure STd, and the discharge contact DCC are formed may be defined as a contact region.

(20) The substrate SUB may include the same material as the substrate SUB described above with reference to FIG. 1. Conductive dopants defining a well region may be injected into the substrate SUB. The conductive dopants defining the well region may be an n-type impurity or a p-type impurity. The well region of the substrate SUB may be divided into active regions ACT1 and ACT2 defined by isolation layers ISO. The isolation layers ISO may include an insulating material embedded in the substrate SUB. The active regions ACT1 and ACT2 may include a first active region ACT1 overlapping with the discharge contact DCC and one or more second active regions ACT2 overlapping with the cell stacked structure STc.

(21) The source layers SLa and SLb may be disposed to be spaced apart from the substrate SUB by the peripheral circuit structure PC and a lower insulating structure LIL that are interposed between the source layers SLa and SLb and the substrate SUB.

(22) The peripheral circuit structure PC may include a transistor TR as described above with

reference to FIG. 1. The transistor TR may include a peripheral-gate insulating layer PGI disposed over the second active region ACT2, a peripheral-gate electrode PG disposed over the peripheral-gate insulating layer PGI, and first and second junctions Jn1 and Jn2 disposed at opposite sides of the peripheral-gate electrode PG, in the second active region ACT2. The first and second junctions Jn1 and Jn2 may be regions defined by injecting the n-type or p-type impurity into the second active region ACT2. One of the first and second junctions Jn1 and Jn2 may serve as a source junction and the other of the first and second junctions Jn1 and Jn2 may serve as a drain junction. (23) The peripheral circuit structure PC may include connecting lines PCL and peripheral contact plugs PCP that are coupled to the transistor TR. As described above with reference to FIG. 1, the peripheral circuit structure PC may include a resistor and a capacitor in addition to the transistor TR and the connecting lines PCL and the peripheral contact plugs PCP that are coupled to the transistor TR.

(24) A conductive impurity may be injected into the first active region ACT1. According to an embodiment, a discharge impurity region DCI may be defined in the first active region ACT1. The discharge impurity region DCI may include conductive impurities forming a PN diode. The discharge impurity region DCI may be used as a path through which charges accumulated in the source layers SLa and SLb are discharged.

(25) The above-described peripheral circuit structure PC may be covered with the lower insulating structure LIL disposed between the source layers SLa and SLb and the substrate SUB. The lower insulating structure LIL may extend to cover the discharge impurity region DCI. The lower insulating structure LIL may include multiple insulating layers that are stacked on top of each other.

(26) The source layers SLa and SLb may be disposed over the lower insulating structure LIL. Each of the source layers SLa and SLb may include two or more semiconductor layers L1, L2, and L3.

(27) For example, the source layer SLa may include first, second, and third semiconductor layers L1, L2, and L3 sequentially stacked over the lower insulating structure LIL. Each of the first and second semiconductor layers L1 and L2 may be a doped semiconductor layer including a source dopant. According to an embodiment, each of the first and second semiconductor layers L1 and L2 may include a doped silicon layer including an n-type impurity. The third semiconductor layer L3 may be omitted in some embodiments. The third semiconductor layer L3 may include at least one of an n-type doped silicon layer and an undoped silicon layer.

(28) For example, the source layer SLb may be configured to include the first, second, and third semiconductor layers L1, L2, and L3, a protective layer PT1 stacked between the first and second semiconductor layers L1 and L2, and a protective layer PT2 stacked between the second and third semiconductor layers L2 and L3. Each of the protective layers PT1 and PT2 may include an oxide layer. The second semiconductor layer L2 included in the source layer SLb may be replaced by a sacrificial layer.

(29) The first semiconductor layer L1, the second semiconductor layer L2, and the third semiconductor layer L3 of the source layer SLa may be electrically coupled to the first semiconductor layer L1, the second semiconductor layer L2, and the third semiconductor layer L3 of the source layer SLb, respectively.

(30) The source layer SLb may be penetrated by the discharge contact DCC. The discharge contact DCC may pass through the lower insulating structure LIL to contact the discharge impurity region DCI of the substrate SUB. The discharge contact DCC may directly contact the discharge impurity region DCI and the source layer SLb. The discharge contact DCC may couple the source layer SLb to the discharge impurity region DCI. Accordingly, charges accumulated in the source layers SLa and SLb may be discharged to the substrate SUB through the discharge impurity region DCI via the discharge contact DCC.

(31) The discharge contact DCC may include first, second, third, fourth, and fifth patterns P1, P2, P3, P4, and P5 that are sequentially stacked on top of each other. The first and third patterns P1 and

P3 may be disposed in the lower insulating structure LIL and may be respectively disposed in levels in which the peripheral contact plugs PCP are disposed. The second and fourth patterns P2 and P4 may be disposed in the lower insulating structure LIL and may be respectively disposed in levels in which the connecting lines PCL are disposed. The fifth pattern P5 may pass through the source layer SLb and extend into the lower insulating structure LIL to contact the fourth pattern P4.

(32) The dummy stacked structure STd may overlap the discharge contact DCC. The dummy stacked structure STd may extend to cover a first region of the source layer SLb, that overlaps the discharge impurity region DCI, and the discharge contact DCC. The dummy stacked structure STd may include dummy interlayer insulating layers ILDD and sacrificial insulating layers SC alternately stacked on each other over the first region of the source layer SLb and the discharge contact DCC.

(33) A sidewall of the fifth pattern P5 of the discharge contact DCC may be surrounded by a dielectric layer D. The fifth pattern P5, the dielectric layer D, and the source layer SLb may serve as a capacitor C. The capacitor C is described in more detail below with reference to FIG. 3.

(34) The cell stacked structure STc may include interlayer insulating layers ILDC and conductive patterns CP1 to CPn alternately stacked on each other over a second region of the source layer SLa, where n is a natural number of 2 or more. The cell stacked structure STc may be disposed not to overlap the discharge contact DCC. The cell stacked structure STc may be disposed in the same level as the dummy stacked structure STd. The interlayer insulating layers ILDC may be disposed in the same levels as the dummy interlayer insulating layers ILDD and the conductive patterns CP1 to CPn may be disposed in the same levels as the sacrificial insulating layers SC.

(35) The interlayer insulating layers ILDC and the dummy interlayer insulating layers ILDD may include the same material and may be formed by the same process. The sacrificial insulating layers SC may include a material having a different etch rate from the interlayer insulating layers ILDC and the dummy interlayer insulating layers ILDD. For example, the interlayer insulating layers ILDC and the dummy interlayer insulating layers ILDD may include a silicon oxide and the sacrificial insulating layers SC may include a silicon nitride.

(36) Each of the conductive patterns CP1 to CPn may include various conductive materials such as a doped silicon layer, a metal layer, a metal silicide layer, and a barrier layer, and may include two or more conductive materials. For example, each of the conductive patterns CP1 to CPn may include tungsten and a titanium nitride (TiN) layer surrounding a surface of tungsten. Tungsten is low-resistance metal and may lower a resistance of the conductive patterns CP1 to CPn. The titanium nitride (TiN) layer may serve as a barrier layer and may prevent tungsten from directly contacting the interlayer insulating layers ILDC.

(37) The conductive patterns CP1 to CPn may serve as gate electrodes of a cell string. The gate electrodes of the cell string may include source select lines, word lines, and drain select lines. The source select lines may serve as gate electrodes of source select transistors, the drain select lines may serve as gate electrodes of drain select transistors, and the word lines may serve as gate electrodes of memory cells.

(38) The cell stacked structure STc may surround channel structures CH. In other words, the channel structures CH may pass through the cell stacked structure STc and a part of the source layer SLa. Each of the channel structures CH may include a channel semiconductor pattern SE. The channel semiconductor pattern SE may include a silicon layer. A central region of the channel semiconductor pattern SE may be filled with a core insulating layer CO. The core insulating layer CO may be formed to have a smaller height than the channel semiconductor pattern SE. A central region of an upper part of the channel semiconductor pattern SE that extends upwards to protrude farther than the core insulating layer CO may be filled with a doped semiconductor pattern DP disposed on the core insulating layer CO. The doped semiconductor pattern DP may include an n-type doped silicon layer. The channel semiconductor pattern SE of each of the channel structures CH may serve as a channel region of the cell string and the doped semiconductor pattern DP of

each of the channel structures CH may serve as a drain junction of the cell string. A sidewall of each of the channel structures CH may be surrounded by a memory layer ML.

(39) The channel structures CH may pass through the cell stacked structure STc and extend into the source layer SLa. A sidewall of each of the channel structures CH that overlaps the source layer SLa may directly contact the source layer SLa. According to an embodiment, the second semiconductor layer L2 of the source layer SLa may directly contact a sidewall of the channel semiconductor pattern SE that overlaps the second semiconductor layer L2. According to the above-described embodiment, the memory layer ML may be divided into a first memory pattern ML1 and a second memory pattern ML2 by the second semiconductor layer L2. The first memory pattern ML1 may be disposed between each of the channel structures CH and the cell stacked structure STc and may extend between each of the channel structures CH and the third semiconductor layer L3. The second memory pattern ML2 may be disposed between each of the channel structures CH and the first semiconductor layer L1.

(40) A slit SI may be filled with a source contact structure SCT. The source contact structure SCT may be spaced apart from the cell stacked structure STc by a sidewall insulating layer SWI formed on a sidewall of the slit SI. The sidewall insulating layer SWI may be penetrated by the source contact structure SCT. The source contact structure SCT may extend to contact the source layer SLa. The source contact structure SCT may include a single type of a conductive material or two or more types of conductive materials. A conductive material for the source contact structure SCT may include a doped silicon layer, a metal layer, a metal silicide layer, and a barrier layer. For example, the source contact structure SCT may include a doped silicon layer contacting the source layer SLa and a metal layer disposed over the doped silicon layer.

(41) An upper insulating layer UIL may include a single insulating layer or two or more insulating layers. For example, the upper insulating layer UIL may include an oxide layer. The upper insulating layer UIL may be penetrated by bit line contact plugs BCT. Each of the bit line contact plugs BCT may be coupled to the doped semiconductor pattern DP of each of the channel structures CH.

(42) FIG. 3 is an enlarged cross-sectional diagram of the capacitor C shown in FIG. 2.

(43) Referring to FIG. 3, the dielectric layer D may be disposed at an interface between the fifth pattern P5 and the first, second, and third semiconductor layers L1, L2, and L3 of the source layer SLb shown in FIG. 2. For example, the dielectric layer D may be formed to surround a sidewall of the fifth pattern P5 having a cylindrical or frustum shape, a square pillar shape, or a linear pillar shape extending in a first direction parallel to the substrate SUB. The fifth pattern P5 may serve as a first electrode 1st_EL of the capacitor and the first, second, and third semiconductor layers L1, L2, and L3 of the source layer SLb shown in FIG. 2 together may serve as a second electrode 2nd_EL of the capacitor.

(44) In other words, a part of a discharge contact and a source layer penetrated by the discharge contact may serve as electrodes of a capacitor.

(45) FIGS. 4A to 4G are diagrams illustrating a method of manufacturing a semiconductor device according to an embodiment.

(46) Referring to FIG. 4A, the peripheral circuit structure PC and the first, second, third, and fourth patterns P1, P2, P3, and P4 may be formed over the substrate SUB including the active regions ACT1 and ACT2 that are defined by the isolation layers ISO. The peripheral circuit structure PC and the first, second, third, and fourth patterns P1, P2, P3, and P4 may be covered with the lower insulating structure LIL.

(47) The active regions ACT1 and ACT2 may include the first active region ACT1 and the second active regions ACT2. The first active region ACT1 may include the discharge impurity region DCI and each of the second active regions ACT2 may include the junctions Jn1 and Jn2. A region overlapping the first active region ACT1 may be defined as a contact region and a region overlapping the second active regions ACT2 may be defined as a memory cell region.

(48) The isolation layers ISO, the active regions ACT1 and ACT2, the discharge impurity region DCI, the junctions Jn1 and Jn2, the peripheral circuit structure PC, and the lower insulating structure LIL are described above in detail with reference to FIG. 1 and/or FIG. 2. Accordingly, any repetitive detailed description of each of these components already described above will be omitted for the sake of brevity.

(49) The first, second, third, and fourth patterns P1, P2, P3, and P4 may include a conductive material and may be sequentially stacked over the discharge impurity region DCI. The first pattern P1 that is disposed in the lowermost level among the first, second, third, and fourth patterns P1, P2, P3, and P4 may directly contact the discharge impurity region DCI.

(50) Subsequently, a lower stacked structure 100 may be formed over the lower insulating structure LIL. The lower stacked structure 100 may include a lower semiconductor layer 101, a sacrificial layer 105, and an upper semiconductor layer 109 sequentially stacked over each other. Before the sacrificial layer 105 is deposited over the lower semiconductor layer 101, a first protective layer 103 may be formed on the lower semiconductor layer 101. Before the upper semiconductor layer 109 is formed over the sacrificial layer 105, a second protective layer 107 may be formed over the sacrificial layer 105.

(51) The lower semiconductor layer 101 may include a doped semiconductor layer including a conductive impurity. For example, the lower semiconductor layer 101 may include an n-type doped silicon layer. The sacrificial layer 105 may include a material having a different etch rate from the first protective layer 103 and the second protective layer 107. The first protective layer 103 and the second protective layer 107 may include materials having different etch rates from the lower semiconductor layer 101 and the upper semiconductor layer 109, respectively. For example, the sacrificial layer 105 may include an undoped silicon layer and each of the first protective layer 103 and the second protective layer 107 may include an oxide layer. For example, the upper semiconductor layer 109 may include a doped silicon layer or an undoped silicon layer.

(52) Subsequently, an opening 115 that passes through a part of the lower stacked structure 100 which overlaps the discharge impurity region DCI to expose the lower insulating structure LIL may be formed. A cross section of the opening 115 may have a circular shape, a rectangular shape, or a linear shape extending in a plane parallel to the substrate SUB. The opening 115 may extend into the lower insulating structure LIL to have a predetermined depth. The opening 115 may expose the fourth pattern P4 that is disposed in the uppermost level among the first, second, third, and fourth patterns P1, P2, P3, and P4.

(53) Referring to FIG. 4B, a dielectric layer 117 may be formed on a sidewall of the opening 115 shown in FIG. 4A. A high dielectric material such as Ta.sub.2O.sub.5, Al.sub.2O.sub.3, La.sub.2O.sub.3, HfO.sub.2, SrTiO.sub.3, BST, and ZrO.sub.2 may be used for the dielectric layer 117 or a ferroelectric material such as PZT, BTO, BNT, PLZT, SBT, and BLT may be used for the dielectric layer 117.

(54) Subsequently, a conductive pattern 119 may be formed to completely fill the opening 115 shown in FIG. 4A.

(55) Referring to FIG. 4C, a first upper stacked structure 120 may be formed over the lower stacked structure 100. The first upper stacked structure 120 may include first material layers 121 and second material layers 123 alternately stacked on each other. The first material layers 121 and the second material layers 123 may extend to overlap the conductive pattern 119.

(56) The first material layers 121 and the second material layers 123 may include different materials. According to an embodiment, the first material layers 121 may include an insulating material and the second material layers 123 may include a sacrificial insulating material having a different etch rate from the first material layers 121. For example, each of the first material layers 121 may include a silicon oxide and each of the second material layers 123 may include a silicon nitride.

(57) Subsequently, first channel holes H1 passing through the first upper stacked structure 120 to

extend into the lower stacked structure **100** may be formed. The first channel holes **H1** may pass through the upper semiconductor layer **109**, the second protective layer **107**, the sacrificial layer **105**, and the first protective layer **103** of the lower stacked structure **100**. The first channel holes **H1** may extend into the lower semiconductor layer **101** of the lower stacked structure **100**.

(58) Referring to FIG. **4D**, a second upper stacked structure **130** may be formed over the first upper stacked structure **120** after the first channel holes **H1** shown in FIG. **4C** are filled with a sacrificial layer. The second upper stacked structure **130** may include first material layers **133** and second material layers **131** alternately stacked on each other.

(59) The first material layers **133** and the second material layers **131** may include different materials. According to an embodiment, the first material layers **133** may include an insulating material and the second material layers **131** may include a sacrificial insulating material having a different etch rate from the first material layers **133**. For example, each of the first material layers **133** may include a silicon oxide and each of the second material layers **131** may include a silicon nitride. The first material layers **133** of the second upper stacked structure **130** may include the same material as the first material layers **121** of the first upper stacked structure **120**. The second material layers **131** of the second upper stacked structure **130** may include the same material as the second material layers **123** of the first upper stacked structure **120**.

(60) Subsequently, second channel holes **H2** passing through the second upper stacked structure **130** to expose the sacrificial layer that fills the first channel holes **H1** shown in FIG. **4C** may be formed. Subsequently, the exposed sacrificial layer may be removed. Accordingly, the second channel holes **H2** may extend into the first upper stacked structure **120** and the lower stacked structure **100**. Each of the second channel holes **H2** may have a bottleneck pattern at a boundary between the first upper stacked structure **120** and the second upper stacked structure **130**.

(61) Referring to FIG. **4E**, a memory layer **135** may be conformally formed on a surface of each of the second channel holes **H2** shown in FIG. **4D**. For an embodiment, this means the memory layer **135** follows the contour of each of the second channel holes **H2**. The memory layer **135** may include a tunnel insulating layer, a data storage layer, and a blocking insulating layer.

(62) A channel semiconductor pattern **137** may be formed in a central region of each of the second channel holes which is opened by the memory layer **135**. The channel semiconductor pattern **137** may be formed to have a pillar shape filling the central region of each of the second channel holes which is opened by the memory layer **135**. Alternatively, the channel semiconductor pattern **137** may be conformally formed along a surface of the memory layer **135** and may open the central region of each of the second channel holes. The central region of each of the second channel holes which is opened by the channel semiconductor pattern **137** may be filled with a core insulating layer **139**. The core insulating layer **139** may be formed to have a height less than that of the channel semiconductor pattern **137** and that of each of the second channel holes. When the core insulating layer **139** has the height less than that of the channel semiconductor pattern **137** and that of each of the second channel holes, a doped semiconductor pattern **141** may be formed on the core insulating layer **139**. The doped semiconductor pattern **141** may be surrounded by an upper portion of the channel semiconductor pattern **137** which extends to protrude farther than the core insulating layer **139**.

(63) The channel semiconductor pattern **137** may include a silicon layer. The doped semiconductor pattern **141** may include an n-type doped silicon layer. The core insulating layer **139** may include an oxide.

(64) Referring to FIG. **4F**, the slit **SI** passing through the second upper stacked structure **130** and the first upper stacked structure **120** which are formed in the memory cell region may be formed and a sidewall insulating layer **145** may be formed on a sidewall of the slit **SI**. The sidewall insulating layer **145** may be formed to expose a bottom of the slit **SI**. The lower stacked structure **100** may be exposed through the bottom of the slit **SI** which is exposed by the sidewall insulating layer **145**.

(65) Subsequently, the upper semiconductor layer **109** and the second protective layer **107** that are exposed through the slit SI may be etched, thereby exposing the sacrificial layer **105** in the memory cell region.

(66) Subsequently, a horizontal space **143** may be formed by removing the sacrificial layer **105** which is exposed. The sacrificial layer **105** in the contact region might not be removed and may remain. The first protective layer and the second protective layer in the memory cell region may prevent a loss of the upper semiconductor layer **109** and the lower semiconductor layer **101** during a process of removing the sacrificial layer **105** in the memory cell region.

(67) According to another embodiment, the sacrificial layer **105** in the contact region may also be removed when the process of removing the sacrificial layer **105** in the memory cell region is performed.

(68) Subsequently, a part of the memory layer which is exposed through the horizontal space **143** may be etched to expose the channel semiconductor pattern **137**. The memory layer may be divided into a first memory pattern **135a** and a second memory pattern **135b** by an etching process.

(69) The first protective layer and the second protective layer in the memory cell region may be removed at the same time during the etching process of the memory layer.

(70) Referring to FIG. 4G, a source semiconductor layer **151** may be formed by introducing a conductive material into the horizontal space **143** shown in FIG. 4F through the slit SI. The source semiconductor layer **151** may contact a sidewall of the channel semiconductor layer **137**, the lower semiconductor layer **101**, and the upper semiconductor layer **109**. The source semiconductor layer **151** may be formed by a chemical vapor deposition method or a growth method using each of the channel semiconductor layer **137**, the lower semiconductor layer **101**, and the upper semiconductor layer **109** as a seed layer. The source semiconductor layer **151** may include a conductive dopant. For example, the source semiconductor layer **151** may include an n-type doped silicon layer. The conductive dopant in the source semiconductor layer **151** may diffuse, by heat, into the upper semiconductor layer **109** and the channel semiconductor layer **137** that contact the source semiconductor layer **151**.

(71) As described above in another embodiment of FIG. 4F, in a case where the sacrificial layer **105** in the contact region is also removed when the process of removing the sacrificial layer **105** in the memory cell region is performed, the source semiconductor layer **151** may be formed to fill a space from which the sacrificial layer **105** is removed.

(72) Subsequently, a source contact structure **147** that contacts the source semiconductor layer **151** and extends along the sidewall insulating layer **145** may be formed by filling the slit SI with a conductive material.

(73) Subsequently, an etching process may be performed to expose a sidewall of each of the first upper stacked structure **120** and the second upper stacked structure **130** that are stacked in the memory cell region and the second material layers of the first upper stacked structure **120** and the second material layers of the second upper stacked structure **130** that are exposed by the etching process may be removed. Subsequently, spaces from which the second material layers of the first upper stacked structure **120** and the second material layers of the second upper stacked structure **130** are removed may be filled with a conductive material, thereby forming gate patterns for word lines.

(74) The semiconductor device according to the embodiment shown in FIGS. 2 and 3 may be formed using processes according to the embodiments shown in FIGS. 4A to 4G.

(75) FIGS. 5A to 5C are layout views illustrating various embodiments of a discharge contact.

(76) In the embodiment described above with reference to FIG. 4B, when the process of filling the opening with the dielectric layer **117** and the conductive pattern **119** is performed, a capacitor having one of various patterns according to embodiments shown in FIGS. 5A to 5C may be formed.

(77) For example, when the opening is of a circular hole type, the conductive pattern **119** may be

formed to have a circular cross section as shown in FIG. 5A, and the dielectric layer **117** may surround a sidewall of the conductive pattern **119** having the circular cross section. In other words, the conductive pattern **119** may be formed to have a cylindrical or frustum shape and the dielectric layer **117** may surround the sidewall of the conductive pattern **119** having the cylindrical or frustum shape.

(78) In other examples, when the opening is of a square hole type, the conductive pattern **119** may be formed to have a square cross section as shown in FIG. 5B, and the dielectric layer **117** may surround sidewalls of the conductive pattern **119** having the square cross section. In other words, the conductive pattern **119** may be formed to have a square pillar shape and the dielectric layer **117** may surround the sidewalls of the conductive pattern **119**.

(79) In other examples, when the opening is of a linear type extending in one direction, the conductive pattern **119** may be formed to have a linear cross section that has a predetermined width as shown in FIG. 5C, and the dielectric layer **117** may surround sidewalls of the conductive pattern **119** having the linear cross section that has the predetermined width. Linear as used herein with respect to the cross-sectional shape of the discharge contact means that a first dimension of the cross-section is substantially longer than a second dimension of the cross-section, as illustrated, for example, in FIG. 5C.

(80) FIG. 6 is a block diagram illustrating a configuration of a memory system **1000** according to an embodiment.

(81) Referring to FIG. 6, the memory system **1000** may include a memory device **1200** and a controller **1100**.

(82) The memory device **1200** may be used to store data information having various data formats such as a text format, a graphical format, and a software code format. The memory device **1200** may be the semiconductor device described above with reference to FIGS. 1 to 3 and may be manufactured by the manufacturing method described above with reference to FIGS. 4A to 4G. Because the memory device **1200** is configured and manufactured in the same manner as described above, a detailed description thereof will be omitted here.

(83) The controller **1100** may be coupled to a host and the memory device **1200** and configured to access the memory device **1200** in response to a request from the host. For example, the controller **1100** may control read, write, erase, and background operations of the memory device **1200**.

(84) The controller **1100** may include Random Access Memory (RAM) **1110**, a Central Processing Unit (CPU) **1120**, a host interface **1130**, an Error Correction Code (ECC) circuit **1140**, and a memory interface **1150**.

(85) The RAM **1110** may serve as operating memory of the CPU **1120**, cache memory between the memory device **1200** and the host, buffer memory between the memory device **1200** and the host, or the like. The RAM **1110** may be replaced with Static Random Access Memory (SRAM), Read Only Memory (ROM), or the like.

(86) The CPU **1120** may control overall operations of the controller **1100**. For example, the CPU **1120** may operate firmware such as a Flash Translation Layer (FTL) stored in the RAM **1110**.

(87) The host interface **1130** may interface with the host. For example, the controller **1100** may communicate with the host through at least one of various interface protocols such as a Universal Serial Bus (USB) protocol, a MultiMedia Card (MMC) protocol, a Peripheral Component Interconnect (PCI) protocol, a PCI Express (PCI-e) protocol, an Advanced Technology Attachment (ATA) protocol, a Serial-ATA protocol, a Parallel-ATA protocol, a Small Computer System Interface (SCSI) protocol, an Enhanced Small Disk Interface (ESDI) protocol, and an Integrated Drive Electronics (IDE) protocol, and a private protocol.

(88) The ECC circuit **1140** may detect and correct errors in data read from the memory device **1200** by using an Error Correction Code (ECC).

(89) The memory interface **1150** may interface with the memory device **1200**. For example, the memory interface **1150** may include a NAND interface or a NOR interface.

(90) The controller **1100** may further include buffer memory (not illustrated) for temporarily storing data. The buffer memory may be used to temporarily store data to be transferred to an external device through the host interface **1130** or data to be transferred from the memory device **1200** through the memory interface **1150**. In addition, the controller **1100** may further include ROM which stores code data to interface with the host.

(91) Because the memory system **1000** includes the memory device **1200** having improved integration density and characteristics, integration density and characteristics of the memory system **1000** may also be improved.

(92) FIG. 7 is a block diagram illustrating a configuration of a memory system **1000'** according to an embodiment. Hereinafter, any repetitive detailed descriptions of components already mentioned above will be omitted.

(93) Referring to FIG. 7, the memory system **1000'** according to an embodiment may include a memory device **1200'** and the controller **1100**. In addition, the controller **1100** may include the RAM **1110**, the CPU **1120**, the host interface **1130**, the ECC circuit **1140**, and the memory interface **1150**.

(94) The memory device **1200'** may be a non-volatile memory device, may be the semiconductor device described above with reference to FIGS. 1 to 3, and may be manufactured by the manufacturing method described above with reference to FIGS. 4A to 4G. Because the memory device **1200'** is configured and manufactured in the same manner as described above, a detailed description thereof will be omitted here.

(95) Furthermore, the memory device **1200'** may be a multi-chip package including a plurality of memory chips. The plurality of memory chips may be divided into a plurality of groups, which may communicate with the controller **1100** through first to kth channels CH1 to CHk, respectively. In addition, memory chips included in a single group may communicate with the controller **1100** through a common channel. The memory system **1000'** may be modified such that a single memory chip may be coupled to a single channel.

(96) Because the memory system **1000'** includes the memory device **1200'** having improved integration density and characteristics, integration density and characteristics of the memory system **1000'** may also be improved. In addition, because the memory device **1200'** is formed into a multi-chip package, data storage capacity and driving speed of the memory system **1000'** may be increased.

(97) FIG. 8 is a block diagram illustrating a configuration of a computing system **2000** according to an embodiment. Hereinafter, any repetitive detailed descriptions of components already mentioned above will be omitted.

(98) Referring to FIG. 8, the computing system **2000** may include a memory device **2100**, a Central Processing Unit (CPU) **2200**, Random Access Memory (RAM) **2300**, a user interface **2400**, a power supply **2500**, and a system bus **2600**.

(99) The memory device **2100** may store data provided via the user interface **2400**, data processed by the CPU **2200**, or the like. In addition, the memory device **2100** may be electrically coupled to the CPU **2200**, the RAM **2300**, the user interface **2400**, the power supply **2500**, and the like through the system bus **2600**. For example, the memory device **2100** may be coupled to the system bus **2600** via a controller (not shown), alternatively, directly coupled to the system bus **2600**. When the memory device **2100** is directly coupled to the system bus **2600**, functions of the controller may be performed by the CPU **2200** and the RAM **2300**.

(100) The memory device **2100** may be a non-volatile memory device, may be the semiconductor device described above with reference to FIGS. 1 to 3, and may be manufactured by the manufacturing method described above with reference to FIGS. 4A to 4G. Because the memory device **2100** is configured and manufactured in the same manner as described above, a detailed description thereof will be omitted here.

(101) As described above with reference to FIG. 7, the memory device **2100** may be a multi-chip

package including a plurality of memory chips.

(102) The computing system **2000** having the above-mentioned configuration may be provided as one of various elements of an electronic device such as a computer, an Ultra Mobile PC (UMPC), a workstation, a net-book, a Personal Digital Assistant (PDA), a portable computer, a web tablet, a wireless phone, a mobile phone, a smart phone, an e-book, a Portable Multimedia Player (PMP), a game console, a navigation device, a black box, a digital camera, a 3-dimensional television, a digital audio recorder, a digital audio player, a digital picture recorder, a digital picture player, a digital video recorder, a digital video player, a device capable of transmitting/receiving information in an wireless environment, one of various electronic devices for forming a home network, one of various electronic devices for forming a computer network, one of various electronic devices for forming a telematics network, an RFID device, or the like.

(103) As described above, because the computing system **2000** includes the memory device **2100** having improved integration density and characteristics, characteristics of the computing system **2000** may also be improved.

(104) FIG. **9** is a block diagram illustrating a computing system **3000** according to an embodiment.

(105) Referring to FIG. **9**, the computing system **3000** may include a software layer which has an operating system **3200**, an application **3100**, a file system **3300**, and a translation layer **3400**. In addition, the computing system **3000** may include a hardware layer such as a memory device **3500**.

(106) The operating system **3200** may manage software and hardware resources of the computing system **3000**. The operating system **3200** may control program execution of a central processing unit. The application **3100** may include various application programs executed by the computing system **3000**. The application **3100** may be a utility executed by the operating system **3200**.

(107) The file system **3300** may refer to a logical structure configured to manage data and files present in the computing system **3000**. The file system **3300** may organize files or data to be stored in the memory device **3500** according to given rules. The file system **3300** may be determined depending on the operating system **3200** used in the computing system **3000**. For example, when the operating system **3200** is a Microsoft Windows-based system, the file system **3300** may be a File Allocation Table (FAT), an NT file system (NTFS), or the like. In addition, when the operating system **3200** is a Unix/Linux-based system, the file system **3300** may be an extended file system (EXT), a Unix File System (UFS), a Journaling File System (JFS), or the like.

(108) FIG. **9** illustrates the operating system **3200**, the application **3100**, and the file system **3300** in separate blocks. However, the application **3100** and the file system **3300** may be included in the operating system **3200**.

(109) The translation layer **3400** may translate an address into a suitable form for the memory device **3500** in response to a request from the file system **3300**. For example, the translation layer **3400** may translate a logical address generated by the file system **3300** into a physical address of the memory device **3500**. Mapping information of the logical address and the physical address may be stored in an address translation table. For example, the translation layer **3400** may be a Flash Translation Layer (FTL), a Universal Flash Storage Link Layer (ULL), or the like.

(110) The memory device **3500** may be a non-volatile memory device, may be the semiconductor device described above with reference to FIGS. **1** to **3**, and may be manufactured by the manufacturing method described above with reference to FIGS. **4A** to **4G**. Because the memory device **3500** is configured and manufactured in the same manner as described above, a detailed description thereof will be omitted.

(111) The computing system **3000** having the above-described configuration may be divided into an operating system layer that is operated in an upper level region and a controller layer that is operated in a lower level region. The application **3100**, the operating system **3200**, and the file system **3300** may be included in the operating system layer, and may be driven by operating memory of the computing system **3000**. The translation layer **3400** may be included in the operating system layer or the controller layer.

(112) As described above, because the computing system 3000 includes the memory device 3500 having improved integration density and characteristics, characteristics of the computing system 3000 may also be improved.

(113) According to embodiments of the present disclosure, a discharge contact formed in a contact region adjacent to a memory cell region may be utilized as a first electrode for a capacitor, and a source layer surrounding a sidewall of the discharge contact may be utilized as a second electrode for the capacitor. A discharge contact so formed may serve to improve the integration density of a semiconductor device.

Claims

1. A semiconductor device, comprising: a first source layer spaced apart from a substrate and disposed in a memory cell region over the substrate; a second source layer spaced apart from the substrate and disposed in a contact region over the substrate; a cell stacked structure including interlayer insulating layers and conductive patterns alternately stacked on each other over the first source layer; a discharge contact passing through at least a part of the second source layer; and a dielectric layer disposed between the second source layer and the discharge contact, wherein the second source layer is a first electrode of a capacitor and the discharge contact is a second electrode of the capacitor.
2. The semiconductor device of claim 1, wherein the first source layer is electrically coupled to the second source layer.
3. The semiconductor device of claim 1, wherein the discharge contact has a cylindrical shape, a frustum shape, a square pillar shape, or a linear pillar shape extending into the second source layer.
4. The semiconductor device of claim 1, wherein the dielectric layer surrounds a sidewall of the discharge contact.
5. The semiconductor device of claim 1, further comprising a channel structure passing through the cell stacked structure and extending into the first source layer.
6. The semiconductor device of claim 5, wherein the channel structure comprises: a core insulating layer extending in a vertical direction; a channel semiconductor layer surrounding a sidewall and a bottom of the core insulating layer; a first memory layer surrounding an upper sidewall of the channel semiconductor layer; and a second memory layer surrounding a lower sidewall and a bottom of the channel semiconductor layer, wherein the first memory layer and the second memory layer are spaced apart from each other to expose a part of a sidewall of the channel semiconductor layer.
7. The semiconductor device of claim 6, wherein the first source layer comprises a first semiconductor layer, a second semiconductor layer, and a third semiconductor layer sequentially stacked on top of each other, and wherein the second semiconductor layer contacts the exposed part of the sidewall of the channel semiconductor layer.
8. The semiconductor device of claim 7, wherein the second source layer comprises the first semiconductor layer, a first protective layer, a sacrificial layer, a second protective layer, and the third semiconductor layer sequentially stacked on top of each other.
9. The semiconductor device of claim 1, further comprising a dummy stacked structure including dummy interlayer insulating layers and sacrificial insulating layers alternately stacked on each other over the second source layer.
10. A semiconductor device, comprising: a source layer spaced apart from a substrate and disposed in a memory cell region and a contact region of the substrate; a cell stacked structure including interlayer insulating layers and conductive patterns alternately stacked on each other over the source layer in the memory cell region; a channel structure passing through at least a part of the cell stacked structure and extending into the source layer in the memory cell region; an electrode passing through at least a part of the source layer in the contact region; and a dielectric layer

disposed between the source layer and the electrode.

11. The semiconductor device of claim 10, wherein the electrode has a cylindrical shape, a frustum shape, a square pillar shape, or a linear pillar shape extending into the source layer.

12. The semiconductor device of claim 10, wherein the dielectric layer surrounds a sidewall of the electrode.

13. The semiconductor device of claim 10, further comprising a dummy stacked structure including dummy interlayer insulating layers and sacrificial insulating layers alternately stacked on each other over the source layer in the contact region.

14. A method of manufacturing a semiconductor device, the method comprising: forming a source layer over a substrate including a memory cell region and a contact region; forming a contact hole passing through the source layer in the contact region; forming a dielectric layer on a sidewall of the contact hole; filling the contact hole with a conductive material; forming a stacked structure in which first material layers and second material layers are alternately stacked on each other over the source layer and the conductive material; and forming a plurality of channel holes passing through the stacked structure to extend into the source layer, in the memory cell region, wherein the dielectric layer is disposed between the source layer and the conductive material.

15. The method of claim 14, wherein forming the source layer comprises sequentially stacking a first semiconductor layer, a first protective layer, a sacrificial layer, a second protective layer, and a second semiconductor layer over the substrate.

16. The method of claim 15, further comprising: forming a channel structure by sequentially stacking a memory layer and a channel semiconductor layer along a sidewall of each of the plurality of channel holes; forming a slit passing through the stacked structure, the second semiconductor layer, and the second protective layer to expose the sacrificial layer; removing the sacrificial layer exposed through the slit to expose a part of a sidewall of the memory layer; etching the exposed part of the sidewall of the memory layer to expose a part of a sidewall of the channel semiconductor layer; and forming a third semiconductor layer contacting the exposed part of the sidewall of the channel semiconductor layer by introducing the conductive material through the slit into a space from which the sacrificial layer is removed.

17. The method of claim 16, further comprising: etching the stacked structure to expose a sidewall of each of the first material layers and the second material layers; removing the second material layers which are exposed; and forming conductive patterns in the spaces from which the second material layers are removed.

18. The method of claim 14, wherein the contact hole is formed to have a cross section having a circular shape, a square shape, or a linear shape in a plane parallel to the substrate.

19. The method of claim 14, wherein the dielectric layer is formed to surround a sidewall of the conductive material.
