

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285917

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

KING; Sean et al.

CONFORMAL LOW TEMPERATURE HERMETIC DIELECTRIC DIFFUSION BARRIERS

Abstract

Conformal hermetic dielectric films suitable as dielectric diffusion barriers over 3D topography. In embodiments, the dielectric diffusion barrier includes a dielectric layer, such as a metal oxide, which can be deposited by atomic layer deposition (ALD) techniques with a conformality and density greater than can be achieved in a conventional silicon dioxide-based film deposited by a PECVD process for a thinner contiguous hermetic diffusion barrier. In further embodiments, the diffusion barrier is a multi-layered film including a high-k dielectric layer and a low-k or intermediate-k dielectric layer (e.g., a bi-layer) to reduce the dielectric constant of the diffusion barrier. In other embodiments a silicate of a high-k dielectric layer (e.g., a metal silicate) is formed to lower the k-value of the diffusion barrier by adjusting the silicon content of the silicate while maintaining high film conformality and density.

Inventors: KING; Sean (Beaverton, OR), YOO; Hui Jae (Portland, OR), KOSARAJU; Sreenivas (Portland, OR), GLASSMAN; Timothy (Portland, OR)

Applicant: Intel Corporation (Santa Clara, CA)

Family ID: 48669055

Appl. No.: 19/175223

Filed: April 10, 2025

Related U.S. Application Data

parent US continuation 18649389 20240429 parent-grant-document US 12300537 child US 19175223

parent US continuation 17855656 20220630 parent-grant-document US 11670545 child US 18137334

parent US continuation 17567762 20220103 parent-grant-document US 11587827 child US 17855656

parent US continuation 16940004 20200727 parent-grant-document US 11251076 child US

17567762
parent US continuation 16702233 20191203 parent-grant-document US 10763161 child US 16940004
parent US continuation 16538666 20190812 parent-grant-document US 10529619 child US 16702233
parent US continuation 15926870 20180320 parent-grant-document US 10438844 child US 16538666
parent US continuation 15686047 20170824 parent-grant-document US 9935002 child US 15926870
parent US continuation 15141522 20160428 parent-grant-document US 9754821 child US 15686047
parent US division 18137334 20230420 parent-grant-document US 12040226 child US 18649389
parent US division 13976835 20130627 parent-grant-document US 9330963 US division PCT/US2011/066252 20111220 child US 15141522

Publication Classification

Int. Cl.: **H01L21/768** (20060101); **H01L21/02** (20060101); **H01L23/00** (20060101); **H01L23/522** (20060101); **H01L23/532** (20060101)

U.S. Cl.:

CPC **H01L21/76831** (20130101); **H01L21/02178** (20130101); **H01L21/022** (20130101); **H01L21/0228** (20130101); **H01L21/76802** (20130101); **H01L21/7682** (20130101); **H01L21/76829** (20130101); **H01L21/76877** (20130101); **H01L23/522** (20130101); **H01L23/5222** (20130101); **H01L23/5226** (20130101); **H01L23/53228** (20130101); **H01L23/53295** (20130101); **H01L23/564** (20130101); H01L2924/0002 (20130101)

Background/Summary

CLAIM OF PRIORITY [0001] The present application is a continuation of U.S. patent application Ser. No. 18/649,389 filed Apr. 29, 2024, which is a divisional of U.S. patent application Ser. No. 18/137,334 filed Apr. 20, 2023, now U.S. Pat. No. 12,040,226 issued Jul. 16, 2024, which is a continuation of U.S. patent application Ser. No. 17/855,656 filed Jun. 30, 2022, now U.S. Pat. No. 11,670,545 issued Jun. 6, 2023, which is a continuation of U.S. patent application Ser. No. 17/567,762 filed Jan. 3, 2022, now U.S. Pat. No. 11,587,827 issued Feb. 21, 2023, which is a continuation of U.S. patent application Ser. No. 16/940,004 filed Jul. 27, 2020, now U.S. Pat. No. 11,251,076 issued Feb. 15, 2022, which is a continuation of U.S. patent application Ser. No. 16/702,233 filed Dec. 3, 2019, now U.S. Pat. No. 10,763,161 issued Sep. 1, 2020, which is a continuation of U.S. patent application Ser. No. 16/538,666 filed Aug. 12, 2019, now U.S. Pat. No. 10,529,619 issued Jan. 7, 2020, which is a continuation of U.S. patent application Ser. No. 15/926,870 filed Mar. 20, 2018, now U.S. Pat. No. 10,438,844 issued Oct. 8, 2019, which is a continuation of U.S. patent application Ser. No. 15/686,047 filed Aug. 24, 2017, now U.S. Pat. No. 9,935,002 issued Apr. 3, 2018, which is a continuation of U.S. patent application Ser. No. 15/141,522 filed Apr. 28, 2016, now U.S. Pat. No. 9,754,821 issued Sep. 5, 2017, which is a divisional of U.S. patent application Ser. No. 13/976,835 filed Jun. 27, 2013, now U.S. Pat. No. 9,330,963 issued May 3, 2016, which is a U.S. National Phase application under 35 U.S.C. § 371 of International Application No. PCT/US2011/066252 filed Dec. 20, 2011, entitled “Conformal

Low Temperature Hermetic Dielectric Diffusion Barriers” the entire contents of which are hereby incorporated by reference herein.

TECHNICAL FIELD

[0002] Embodiments of the present invention generally relate to semiconductor devices, and more particularly to conformal dielectric diffusion barriers.

BACKGROUND

[0003] Microelectronic devices, such as integrated circuits incorporating metal-oxide-semiconductor transistors (MOSFETs), or the like, continue to scale by reducing pitches between adjacent features and incorporating three-dimensional transistor structures (e.g., finFETs). As transistor density and non-planarity increases, so too does the interconnect metallization, increasing interconnect capacitance and making electrical isolation more difficult. Interconnect processes over the last decade have increasingly incorporated “low-k” films (e.g., those below ~3.2) as the material of choice of inter-level dielectrics (ILDs), some further implementing air gap formation whereby voids in the ILD between adjacent metal lines are deliberately introduced. Also, topography present due to radical 3D structures may induce voids and/or defects that need to be sealed/covered by a conformal dielectric layer.

[0004] Plasma enhanced chemical vapor deposition (PECVD) processes are typically used for dielectric deposition in low-k interconnect applications but do not offer high conformality/step coverage. For example, a PECVD low-k film typically has conformality less than 55% (e.g., only approaching 75% with a dep/etch/dep type sequence) where a dielectric has deposited thickness on vertical (e.g., sidewall) surface that is less than 55% of the deposited thickness on a horizontal (e.g., top) surface. CVD or low pressure CVD (LPCVD) techniques offer higher conformality, but require temperatures higher than typically permissible for low-k interconnect applications.

[0005] It is often desirable to provide a hermetic seal with a dielectric layer, for example to prevent out-diffusion of metal (e.g., Cu) from a metal interconnect line into surrounding ILD material, as well as to prevent moisture and wet chemical in-diffusion from surrounding ILD (or from a void in an air gap formation process) into a 3D structure (e.g., metal line, transistor, etc.). Due to difficulties in achieving perfect coverage and film densification over 3D topography, there is therefore a minimum thickness requirement for a dielectric diffusion barrier.

[0006] Materials and techniques to reduce a dielectric diffusion barrier minimum thickness are therefore advantageous.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] Embodiments of the present invention are illustrated by way of example, and not by way of limitation, and can be more fully understood with reference to the following detailed description when considered in connection with the figures in which:

[0008] FIG. 1 is a flow diagram illustrating a method of forming a dielectric diffusion barrier, in accordance with an embodiment;

[0009] FIGS. 2A, 2B, 2C, 2D, 2E, 2F, 2G, and 2H illustrate side views of a cross section through an IC fabricated in accordance with an embodiment of the method illustrated in FIG. 1;

[0010] FIGS. 3A-3B illustrate line graphs for experimental evaluations of dielectric diffusion barrier embodiments, in accordance with embodiments of the present invention; and

[0011] FIG. 4 is a functional block diagram of a mobile computing platform which may incorporate ICs fabricated in accordance with the method illustrated by FIGS. 1 and 2A-2G.

DETAILED DESCRIPTION

[0012] In the following description, numerous details are set forth, however, it will be apparent to one skilled in the art, that the present invention may be practiced without these specific details. In

some instances, well-known methods and devices are shown in block diagram form, rather than in detail, to avoid obscuring the present invention. Reference throughout this specification to “an embodiment” means that a particular feature, structure, function, or characteristic described in connection with the embodiment is included in at least one embodiment of the invention. Thus, the appearances of the phrase “in an embodiment” in various places throughout this specification are not necessarily referring to the same embodiment of the invention. Furthermore, the particular features, structures, functions, or characteristics may be combined in any suitable manner in one or more embodiments. For example, a first embodiment may be combined with a second embodiment anywhere the two embodiments are not mutually exclusive.

[0013] The terms “coupled” and “connected,” along with their derivatives, may be used herein to describe structural relationships between components. It should be understood that these terms are not intended as synonyms for each other. Rather, in particular embodiments, “connected” may be used to indicate that two or more elements are in direct physical or electrical contact with each other. “Coupled” may be used to indicate that two or more elements are in either direct or indirect (with other intervening elements between them) physical or electrical contact with each other, and/or that the two or more elements co-operate or interact with each other (e.g., as in a cause and effect relationship).

[0014] The terms “over,” “under,” “between,” and “on” as used herein refer to a relative position of one material layer with respect to other layers. As such, for example, one layer disposed over or under another layer may be directly in contact with the other layer or may have one or more intervening layers. Moreover, one layer disposed between two layers may be directly in contact with the two layers or may have one or more intervening layers. In contrast, a first layer “on” a second layer is in direct contact with that second layer.

[0015] Described herein are conformal hermetic dielectric films suitable for dielectric diffusion barriers over 3D topography. In embodiments, the dielectric diffusion barrier is a dielectric layer which is deposited by atomic layer deposition (ALD) techniques to achieve a conformality of at least 95% for a thinner contiguous diffusion barrier than can be achieved in a conventional silicon dioxide/nitride/carbide-based film, for example deposited by PECVD or by a repetitive deposition/sputter plasma enhanced chemical vapor deposition (PECVD) process capable of a conformality of no more than 75%. Because the ALD dielectric layer may have a relatively higher dielectric constant than such PECVD films, it may be counter intuitive to employ such a material in structures sensitive to capacitance, however it has been found the excellent step coverage and greater mass/atomic density of certain “high-k” dielectric layer materials enables a hermetic diffusion barrier of reduced thickness. Generally, this high mass and/or high atomic density implies no (or very low) porosity with interstitial spaces in the barrier material being of such a small dimension that it is difficult for diffusing atoms to pass through the barrier material (i.e., a more tortuous diffusion path).

[0016] Thus, for a diffusion barrier, the tradeoff between a moderate k film with only moderately good step coverage and hermeticity and a higher k film with better step coverage and hermeticity can be made favorable. For example, in certain applications, this reduction in thickness of the diffusion barrier enables a net reduction in capacitance of a structure (e.g., an interconnect ILD level) by increasing an available volume for an extremely low dielectric (e.g., a volume for an air gap).

[0017] In further embodiments, the dielectric constant of the diffusion barrier is advantageously reduced by where the barrier is made a multi-layered film including the relatively high-k ALD layer and a low-k or intermediate-k dielectric layer (e.g., a bi-layer). In other embodiments a silicate of the relatively high-k ALD layer is formed to take advantage of the conformality and density of the ALD dielectric, but lower the k-value of the diffusion barrier by adjusting the silicon content of the silicate.

[0018] FIG. 1 is a flow diagram illustrating a method **100** for forming a dielectric diffusion barrier,

in accordance with an embodiment where interconnect metallization in ILD incorporates air gaps between adjacent metal structures of a same metallization layer (e.g., metal lines). A dielectric diffusion barrier is disposed between the air gap sidewalls of the metal lines to protect the interconnect metallization. While the exemplary interconnect embodiments serves as useful illustrations, it is noted that the dielectric diffusion barrier materials and deposition techniques described in the exemplary interconnect context are applicable in many other contexts where a dense, conformal hermetic dielectric diffusion barrier is needed over severe 3D topography. For example, one of skill in the art may readily implement the teachings provided herein to form a diffusion barrier disposed over a finfet, a liner of a shallow trench isolation region, a passivation layer of a waveguide in a photonic integrated circuit, etc. The teachings provided herein are also applicable for some 2D applications such as forming very thin, hermetic Cu capping layers in dual damascene structures.

[0019] Method **100** begins at operation **110** with the formation of a low-k ILD structure. FIG. 2A illustrates a side view of a cross section through an integrated circuit (IC), such as a microprocessor or other logic device, fabricated in accordance with an embodiment of the method **100**. In FIG. 2A, transistors of the IC are disposed in the substrate **201**. The substrate **201** may include any conventional semiconductor substrate (e.g., silicon, Ge, SiGe, SiC, GaAs, InP, GaN, etc.), whether in a bulk or SOI format, as well as polymer substrates (e.g. in TFT applications). Transistors disposed in the substrate **201** may be of any conventional design, such as, but not limited to, planar or non-planar MOSFETs, planar or non-planar high electron mobility transistors (HEMTs), etc.

[0020] Disposed over the substrate **201** is a low-k ILD structure comprising a low-k dielectric layer **210** in which a first metal interconnect level **205** is embedded, for example by any dual damascene process known in the art. In the exemplary embodiment, the low-k dielectric layer **210** is a carbon-doped oxide (SiOC:H) having a dielectric constant in the range of 2.5-3.2, depending on porosity. Of course, other known low-k ILD materials may also be utilized, and indeed in the exemplary embodiment where the low-k dielectric layer **210** is in some respects is sacrificial (as discussed elsewhere herein), it is also possible to use in place of the low-k dielectric layer **210** a layer of a conventional moderate-k dielectric material, such as SiO₂, PSG, BPSG, SiOF, etc. In embodiments, each metal interconnect line **205** comprises a barrier layer, such as tantalum (Ta) or TiN, and a fill metal, such as copper (Cu) or tungsten (W).

[0021] Continuing with the method **100**, at operation **130** trenches are etched into the low-k ILD around the metal interconnects. Generally, operation **130** entails rendering a planar damascene layer non-planar for the sake of introducing voids into spaces between the metal interconnect lines. It is this introduction of extreme topography which provides an exemplary impetus for the highly conformal dielectric diffusion barriers described herein. As one example of forming such trenches, FIG. 2B illustrates a side view of a cross section through the integrated circuit (IC) illustrated in FIG. 2A following deposition of a hard mask layer **220A** over the low-k ILD structure. The hard mask layer **220A** may be any material known in the art to be suitable for such purposes, such as, but not limited to, a low-k SiN:H, SiC:H, SiOC:H, SiCN:H, or SiOCN:H (as the hard mask layer **220A** is typically deposited by PECVD, a significant amount of hydrogen is incorporated into the films). The thickness of the hard mask layer **220A** may range from about 2-50 nm and dielectric constant (k) of the material may range from 4-7. In the exemplary embodiment, thickness is about 8 nm and k is about 4.8. Notably, in addition to aiding patterning, the hardmask layer **220A** also serves to protect the top surface of the metal interconnects from oxidation and corrosion during fabrication. In exemplary embodiment, the hardmask layer **220A** is non-sacrificial, remaining in place to passivate the (Cu) surface of the metal interconnects and should therefore have good adhesion to minimize mechanical and electromigration failures.

[0022] Continuing with the exemplary implementation of operation **130**, FIG. 2C illustrates a deposition of additional masking layers to form a multi-layered mask and patterning of the multi-layered mask. Disposed over the hard mask layer **220A** is a second hard mask layer **220B**, such as,

but not limited to, amorphous carbon (α -C:H), TiN, or TaN. Over the second hard mask layer **220B** is any conventional photoresist **220C**, and an organic anti-reflective coating (ARC), and/or dielectric ARC (DARC) **220D**, such as, but not limited to a silicon-containing material like silicon dioxide, silicon nitride, carbon doped oxide, etc. The patterning is such that openings **225** are formed over the low-k dielectric layer **210** in the spaces between two adjacent metal interconnect lines (e.g., **205A** and **205B**).

[0023] FIG. 2D completes the exemplary implementation of operation **130** with etching of the trenches **230** in the low-k dielectric **210** disposed between adjacent metal interconnect lines **205A**, **205B**. Any plasma-based etches, such as but not limited to fluorinated chemistries (CF.sub.4, C.sub.2F.sub.6, CF.sub.3H, etc.) may be utilized to etch trenches **230** to extend at least partially through the (partially sacrificial) low-k ILD layer **210** from a top surface of the low-k dielectric layer **210**, and may extend completely through the low-k dielectric layer **210** to expose the substrate **201**. It is, of course, understood that the trench **230** can also be formed by any other known technique such as, but not limited to, ion milling and laser ablation. The photoresist **220C**, second hardmask layer **220B** (e.g., TiN), and the other patterning materials are then removed using any combination of dry plasma etching and wet chemical cleans known in the art (typically by an oxygen plasma or hydrogen plasma followed by a wet clean). Following the completion of operation **130**, and as illustrated in FIG. 2D, the low-k ILD structure now includes extreme 3D topography with metal interconnect lines (e.g., Cu) extending upward around trenches (vias) inlaid into the metal interconnect lines **205** where portions of the low-k dielectric layer **210** have been removed. In embodiments, the trench **230** has an aspect ratio of at least 5:1 and greater than 7:1 in the exemplary embodiment. Notably, although the hardmask layer **220A** is retained as a non-sacrificial layer in the exemplary embodiment, the hard mask layer **220A** may not remain intact due to corner rounding during the etching of the trench **230** or may be completely removed by subsequent processing.

[0024] Returning to FIG. 1, the method **100** continues with conformally depositing a hermetic dielectric diffusion barrier. In the exemplary interconnect embodiment, illustrated in FIG. 2E shows the dielectric diffusion barrier **240** forms a contiguous liner in the trench **230**, spanning the space between adjacent metal interconnect lines **205A**, **205B**, as well as covering the hardmask layer **220A**.

[0025] In an embodiment, at least a portion of the hermetic dielectric diffusion barrier **240** is deposited with an ALD process. Though ALD is generally known in the art, it is limited in application by the practical constraints imposed by the availability of acceptable precursors capable of self-limiting reactions to form a film of the desired composition. Thus, while the widespread availability of certain pre-cursors has enabled ALD to become a popular technique for the formation of gate dielectric layers, such has not been true for dielectric materials employed in typical interconnect isolation capacities. For this reason, plasma enhanced ALD (PEALD), a quasi-ALD technique, has been investigated as a means to deposit a wider variety of materials, but films produced by this technique have been found to be uniformly hermetic only at thickness greater than about 16 nm and therefore the quasi-ALD technique is not particularly advantageous for dielectric diffusion barriers. Hermetic barriers at thicknesses less than 5 nm are only possible with PECVD/PEALD technique where the film is deposited on perfectly flat surfaces because of densification of the film from through ion bombardment during the deposition or sputter treatments. However, because this ion bombardment is highly direction, film deposited on ion shadowed surfaces (e.g., near vertical surfaces) are of lower density and not hermetic. In the exemplary embodiments described herein, a true ALD process is employed to form a dielectric diffusion barrier that is hermetic at thicknesses below 10 nm, more particularly below 8 nm, and most particularly below 6 nm. With the high conformality of the ALD process (e.g., 95% or more), it is possible to establish a contiguous, pin-hole free film over extreme 3D topography at these very low film thicknesses.

[0026] In an embodiment, prior to depositing the dielectric diffusion barrier **240**, a dielectric material is deposited by PECVD to avoid direct exposure of any exposed surface of the metal interconnect lines (e.g., Cu) which might be adversely affected by direct exposure to an ALD precursor. If the hardmask **220A** is fully in place and some amount of low-k ILD is preserved on the interconnect line sidewall, the top surface and liner of the interconnect line may be protected. However due to imperfections, some low-k ILD may not remain on the sidewall and the top interconnect surface may be exposed to corner clipping, partial etching or complete removal of the hardmask **220**. Also, low-k ILDs are poor barriers and oxidation of the interconnect liner (Ta/TaN) remains a possibility regardless. Exemplary dielectric materials suitable for this purpose, include, but are not limited to, SiN:H, SiCN:H, SiC:H, SiOC:H (e.g., having a range of dielectric constants described elsewhere herein for the hardmask layer **220A**) and may be deposited by PECVD to a thickness preferably less than 2 nm, though alternate embodiments include depositing the low-k interconnect passivation film to greater thicknesses (e.g., 4 nm-16 nm).

[0027] In an embodiment, at least a portion of the hermetic dielectric diffusion barrier **240** is an ALD dielectric material that has a relatively high dielectric constant compared to silicon-based PECVD films (e.g., greater than 6). There are many such films known in the art to be formable with the ALD technique and generally any of them may be employed as the dielectric diffusion barrier **240**, or a portion thereof. In the exemplary embodiment, the high-k dielectric material is a metal oxide such as, but not limited to, Al.sub.2O.sub.3, MgO.sub.2, and HfO.sub.2, all of which have a dielectric constant well over 10. Other transition metal oxides, such as TiO.sub.2, TaO.sub.2, and ZrO.sub.2, that are also compatible with the ALD technique may be utilized in alternate embodiments.

[0028] Employing a true ALD technique, self-limiting reactions are successively performed during the operation **140**. For example, a 6-10 nm Al.sub.2O.sub.3 film may be deposited as the dielectric diffusion barrier **240** by sequentially pulsing trimethylaluminum (TMA) and H.sub.2O vapor, each precursor participating in a self-limiting reaction to iteratively form a very conformal film. These sequential self-limiting reactions impart the advantageous high conformality to the dielectric diffusion barrier **240** at temperatures below those required to conformally deposit dielectrics in LPCVD processes. Also advantageous, the aluminum atom is large and tightly bonds with neighboring oxygen atoms to form a dense film capable of hermeticity at thicknesses below 8 nm and even below 6 nm (e.g., 3-4 nm). While the exemplary embodiment of Al.sub.2O.sub.3 has been experimentally verified, similar performance is expected of MgO.sub.2 and HfO.sub.2, and may also be expected of other high-k films known in the art to have similar atomic density. Thus, in the exemplary embodiment, ALD is utilized to achieve a contiguous dielectric film over extreme 3D topography even at thicknesses in the 5-10 nm range and the species employed in the ALD technique are ones which form a dense film capable of providing hermeticity at the minimum thickness required to form a physically contiguous film over the topography present.

[0029] While embodiments employing an ALD dielectric layer may of course include more than one type of dielectric material (e.g., a bi-layer of distinct high-k materials), in an exemplary embodiment, an ALD dielectric layer is coupled with a distinct dielectric material layer having a dielectric constant below that of the ALD material. In one such embodiment, the dielectric diffusion barrier **240** includes at least one metal oxide layer **242**, such as Al.sub.2O.sub.3, MgO.sub.2, and HfO.sub.2, and a moderate-k material layer **243** having a dielectric constant below that of the metal oxide but above that of the surrounding low-k dielectric layer (e.g., low-k ILD **210**), as shown in FIG. 2H. In an exemplary embodiment, the moderate-k material is SiON(C):H. In such an embodiment the SiON(C):H layer is formed by first depositing by PECVD a SiO(C):H film and then sputter etching that SiO(C):H film with an plasma including a nitrogen source (e.g., one or more of NH.sub.3, N.sub.2) which sputters away part of the non-conformally deposited material and redistributes it onto topographic sidewalls (e.g., sidewalls of the trench **230**). While the sputter etch densifies the SiOC:H film and incorporates nitrogen to form SiON(C):H, such a

film on its own would not be hermetic on ion-shadowed surfaces unless over 15 nm (e.g., 16 nm and above). However, with hermeticity enhanced by the ALD film and the dielectric constant of this moderate-k material being in the range of 4.4-5.5 the dielectric diffusion barrier **240** may have a reduced total capacitance.

[0030] In embodiments, the SiON(C):H and ALD dielectric form a bi-layer with either the SiON(C):H forming a first layer or the ALD dielectric forming the first layer. In the exemplary embodiment the bi-layer dielectric diffusion barrier **240** includes a first layer of SiON(C):H and the ALD dielectric as a second layer disposed on the first layer. Exemplary thicknesses of the bi-layer dielectric diffusion barrier **240** are between 5 and 10 nm with the SiON(C):H being between 3 and 6 nm (e.g., slightly more than half the total thickness of the dielectric diffusion barrier **240**). In one embodiment where a dielectric layer (e.g., SiOC:H) is first deposited to passivate a metal interconnect line prior to forming the ALD dielectric layer, deposition of the passivating dielectric layer may be transitioned into the first layer of the dielectric diffusion barrier **240** by initiating the nitrogen-based sputter etch process to convert a portion of the passivating dielectric layer into the denser, more conformal SiON(C):H film.

[0031] In further embodiments, the dielectric diffusion barrier **240** is a tri-layer film stack **241** in which the ALD dielectric material (not shown) is disposed between PECVD deposited films (e.g., a base layer of SiON(C):H (not shown) as in the case of a bi-layer embodiment and a cap layer of a SiON(C):H) which may improve adhesion and etch profiles in overlying layer deposited in subsequent operations.

[0032] In another embodiment, the dielectric diffusion barrier **240** includes a silicon alloy of a metal oxide. The silicon alloy of the metal oxide in the exemplary embodiment is formed by ALD (as opposed to an alloy formed by solid state diffusion of a discretely deposited film stack). In one such embodiment, at least one metal oxide is deposited in conjunction with silicon to form a conformal metal silicate film. In such embodiments, the amount of silicon incorporated into the dielectric diffusion barrier **240** may range from 1-90% (atomic) as selected to achieve a desired reduction in the dielectric constant of dielectric diffusion barrier **240**. For example, in one embodiment where the metal oxide is Al.sub.2O.sub.3, silicon is introduced to generate a Al.sub.1-ySi.sub.yO.sub.x dielectric film. In one exemplary Al.sub.1-ySi.sub.yO.sub.x embodiment, the silicon content is at least 50% (atomic) to reduce the dielectric constant of the alloy to below 7 while still providing a hermetic seal at thicknesses below 15 nm, and preferably below 10 nm. For example, during operation **140** an ALD sequence of TMA/H.sub.2O/SiH.sub.4/H.sub.2O may be performed with the duty cycle between TMA and SiH.sub.4 varied to achieve the desired silicon content. In alternative embodiments, other metal silicates can be produced by analogous ALD processes incorporating other exemplary metal oxides (e.g., MgO.sub.2, HfO.sub.2, etc.). In alternative embodiments another alloying species other than silicon is employed to lower the dielectric constant of the dielectric diffusion barrier **240**. For example, any of B.sub.2O.sub.3, BeO.sub.2, Li.sub.2O, Na.sub.2O might be utilized.

[0033] As with a metal oxide layer, the alloyed dielectric utilized in the dielectric diffusion barrier **240** may include a base PECVD layer and/or a cap PECVD layer in addition to the ALD metal silicate layer. For example, a metal silicate layer (Al.sub.1-ySi.sub.yO.sub.x) may be disposed on a SiN:H, SiC:H, SiOC:H, or SiCN:H film or capped with a SiN:H, SiC:H, SiOC:H, or SiCN:H film. As another example, the metal silicate layer (Al.sub.1-ySi.sub.yO.sub.x) is disposed between a cap and a base layer of any of SiN:H, SiC:H, SiOC:H, or SiCN:H.

[0034] Returning to FIG. 1, method **100** continues at operation **150** with a non-conformal deposition of a low-k or moderate-k (e.g., SiO.sub.2, PSG, BPSG, SiOF, polymer, etc.) ILD. In the exemplary interconnect embodiment, it is this non-conformal deposition at operation **150** which is to generate air gaps within the space remaining between the topographic features to reduce the interconnect capacitance relative to the ILD structure illustrated in FIG. 2A. As shown in FIG. 2F, due to the non-conformality of the low-k ILD **250**, an air gap **255** is formed between adjacent metal

interconnect lines **205A**, **205B** in the region of the trench **230** not occupied by the dielectric diffusion barrier **240**. Hence, it should be clear that reducing the thickness of the dielectric diffusion barrier **240** by 1 unit (e.g., 8 nm) can increase the width of the air gap **255** by 2 units (e.g., 16 nm) and therefore result in a net improvement (i.e., reduction) in capacitance even though a high-k material may be introduced to some extent within the dielectric diffusion barrier **240**.

[0035] Referring still to FIG. **2F**, in embodiments the, low-k ILD **250** is SiOC:H with a dielectric constant in the range of 2.5-3.1. In certain other embodiments, the low-k ILD **250** is a porous film having a dielectric constant below about 2.5. As known, in the art, a chemical-mechanical planarization (CMP) process may be employed to planarized the surface of the low-k ILD **250**.

[0036] Returning to FIG. **1**, the method **100** continues at operation **160** where the device is completed with conventional processing and fabrication techniques know in the art. For example, as illustrated in FIG. **2G**, an additional level of metal interconnect **260** is disposed in the low-k ILD **250**. As shown, the metal interconnect **260** is coupled to the metal interconnect **205** by a metal-filled (Cu) via passing through the dielectric diffusion barrier **240** and any remaining hardmask layer **220**. Additional air-gaps may then be formed in the second-level of metal interconnect substantially as described elsewhere herein in the context of operations **110-150**.

[0037] FIGS. **3A-3B** illustrate line graphs for experimental evaluations of dielectric diffusion barrier embodiments, in accordance with embodiments of the present invention. Stress measurements were collected for a film stack including the dielectric diffusion barrier treatment over a thick moisture absorbing oxide which registers a change in stress measured via wafer bow and correlated with moisture content. The FIG. **3A** shows a flat line trend for an ALD layer of Al.sub.2O.sub.3 of 6 nm and greater serve as a moisture diffusion barrier (hermetic barrier). For thicknesses below 6 nm, wafer bow changes over time indicating the moisture is penetrating the Al.sub.2O.sub.3 layer. FIG. **3B** is a line graph for a SiON(C):H/AlO.sub.x bilayer dielectric diffusion barrier. As can be seen, a 6 nm SiON(C):H layer 2 nm AlO.sub.x layer shows little moisture absorption. This represents more than a 60% reduction in thickness of the high-k Al.sub.2O.sub.3 needed to form a conformal barrier and therefore capacitance may be advantageously reduced while still providing an extremely thin hermetic barrier (e.g., 8 nm). For reference, at least 14 nm of SiON(C) is needed to provide similar results. In reference to embodiments of a silicon alloyed metal oxide diffusion barrier (e.g., metal silicate), though not explicitly depicted in a plot it is noted that because SiON layer with an oxygen content twice the nitrogen content has been found to maintain a hermeticity equivalent of SiN compositions, it is expected that metal silicate (e.g., aluminosilicates, Al.sub.1-ySi.sub.yO.sub.x, magnesiosilicates (Mg.sub.1-ySi.sub.yO.sub.x), etc.) films where up to 50% of the metal species is replaced by Si will also maintain the hermeticity of the corresponding metal oxide.

[0038] FIG. **4** illustrates a computing device **1000** in accordance with one implementation of the invention. The computing device **1000** houses a board **1002**. The board **1002** may include a number of components, including but not limited to a processor **1004** and at least one communication chip **1006**. The processor **1004** is physically and electrically coupled to the board **1002**. In some implementations, at least one communication chip **1006** is also physically and electrically coupled to the board **1002**. In further implementations, the communication chip **1006** is part of the processor **1004**.

[0039] Depending on its applications, computing device **1000** may include other components that may or may not be physically and electrically coupled to the board **1002**. These other components include, but are not limited to, volatile memory (e.g., DRAM), non-volatile memory (e.g., ROM), flash memory, a graphics processor, a digital signal processor, a crypto processor, a chipset, an antenna, a display, a touchscreen display, a touchscreen controller, a battery, an audio codec, a video codec, a power amplifier, a global positioning system (GPS) device, a compass, an accelerometer, a gyroscope, a speaker, a camera, and a mass storage device (such as hard disk drive, compact disk (CD), digital versatile disk (DVD), and so forth).

[0040] The communication chip **1006** enables wireless communications for the transfer of data to and from the computing device **1000**. The term “wireless” and its derivatives may be used to describe circuits, devices, systems, methods, techniques, communications channels, etc., that may communicate data through the use of modulated electromagnetic radiation through a non-solid medium. The term does not imply that the associated devices do not contain any wires, although in some embodiments they might not. The communication chip **1006** may implement any of a number of wireless standards or protocols, including but not limited to Wi-Fi (IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The computing device **1000** may include a plurality of communication chips **1006**. For instance, a first communication chip **1006** may be dedicated to shorter range wireless communications such as Wi-Fi and Bluetooth and a second communication chip **1006** may be dedicated to longer range wireless communications such as GPS, EDGE, GPRS, CDMA, WiMAX, LTE, Ev-DO, and others.

[0041] The processor **1004** of the computing device **1000** includes an integrated circuit die packaged within the processor **1004**. In some implementations of the invention, the integrated circuit die of the processor includes one or more devices, such as metal interconnects with a dielectric diffusion barrier disposed there between as described elsewhere herein. The term “processor” may refer to any device or portion of a device that processes electronic data from registers and/or memory to transform that electronic data into other electronic data that may be stored in registers and/or memory.

[0042] The communication chip **1006** also includes an integrated circuit die packaged within the communication chip **1006**. In accordance with another implementation of the invention, the integrated circuit die of the communication chip includes one or more devices such as metal interconnects with a dielectric diffusion barrier disposed there between as described elsewhere herein.

[0043] In further implementations, another component housed within the computing device **1000** may contain an integrated circuit die that includes one or more devices, such as metal interconnects with a dielectric diffusion barrier disposed there between as described elsewhere herein.

[0044] In various implementations, the computing device **1000** may be a laptop, a netbook, a notebook, an ultrabook, a smartphone, a tablet, a personal digital assistant (PDA), an ultra mobile PC, a mobile phone, a desktop computer, a server, a printer, a scanner, a monitor, a set-top box, an entertainment control unit, a digital camera, a portable music player, or a digital video recorder. In further implementations, the computing device **1000** may be any other electronic device that processes data.

[0045] The above description is illustrative, and not restrictive. For example, while flow diagrams in the figures show a particular order of operations performed by certain embodiments of the invention, it should be understood that such order may not be required (e.g., alternative embodiments may perform the operations in a different order, combine certain operations, overlap certain operations, etc.). Furthermore, many other embodiments will be apparent to those of skill in the art upon reading and understanding the above description. Although the present invention has been described with reference to specific exemplary embodiments, it will be recognized that the invention is not limited to the embodiments described, but can be practiced with modification and alteration within the spirit and scope of the appended claims. The scope of the invention should, therefore, be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled.

Claims

1. An integrated circuit structure, comprising: a metal interconnect structure in a first dielectric layer, the first dielectric layer comprising silicon, oxygen and carbon; a second dielectric layer directly on the metal interconnect structure and directly on the first dielectric layer, the second dielectric layer comprising nitrogen and oxygen; a third dielectric layer directly on the second dielectric layer, the third dielectric layer comprising silicon, oxygen and carbon; a fourth dielectric layer directly on the third dielectric layer, the fourth dielectric layer comprising aluminum and oxygen; a fifth dielectric layer directly on the fourth dielectric layer, the fifth dielectric layer comprising silicon, oxygen and carbon; and a conductive via in the fifth dielectric layer and through an opening in the fourth dielectric layer, the third dielectric layer and the second dielectric layer, the conductive via directly on and electrically coupled to the metal interconnect structure.
2. The integrated circuit structure of claim 1, wherein the third dielectric layer has a dielectric constant less than the dielectric constant of the second dielectric layer.
3. The integrated circuit structure of claim 1, wherein the fourth dielectric layer has a dielectric constant greater than a dielectric constant of the third dielectric layer.
4. The integrated circuit structure of claim 1, wherein the third dielectric layer has a dielectric constant less than the dielectric constant of the second dielectric layer, and wherein the fourth dielectric layer has a dielectric constant greater than a dielectric constant of the third dielectric layer.
5. The integrated circuit structure of claim 1, wherein the first dielectric layer is a low-k inter-layer dielectric layer.
6. The integrated circuit structure of claim 1, wherein the fifth dielectric layer is a low-k inter-layer dielectric layer.
7. The integrated circuit structure of claim 1, wherein the first dielectric layer is a first low-k inter-layer dielectric layer, wherein the fifth dielectric layer is a second low-k inter-layer dielectric layer.
8. The integrated circuit structure of claim 1, wherein the conductive via includes a barrier layer comprising tantalum, and a conductive fill comprising copper.
9. The integrated circuit structure of claim 1, wherein the second dielectric layer has a thickness in the range of 2-50 nm.
10. The integrated circuit structure of claim 1, wherein the second dielectric layer further
11. An integrated circuit structure, comprising: a metal interconnect structure in a first low-k dielectric layer, the first low-k dielectric layer comprising silicon, oxygen and carbon; a hardmask layer directly on the metal interconnect structure and directly on the first low-k dielectric layer, the hardmask layer comprising nitrogen and oxygen; an intermediate dielectric layer directly on the hardmask layer, the intermediate dielectric layer comprising silicon, oxygen and carbon; a metal oxide layer directly on the intermediate dielectric layer, the metal oxide layer comprising aluminum and oxygen; a second low-k dielectric layer directly on the metal oxide layer, the second low-k dielectric layer comprising silicon, oxygen and carbon; and a conductive via in the second low-k dielectric layer and through an opening in the metal oxide layer, the intermediate dielectric layer and the hardmask layer, the conductive via directly on and electrically coupled to the metal interconnect structure.
12. The integrated circuit structure of claim 11, wherein the intermediate dielectric layer has a dielectric constant less than the dielectric constant of the hardmask layer.
13. The integrated circuit structure of claim 11, wherein the metal oxide layer has a dielectric constant greater than a dielectric constant of the intermediate dielectric layer.
14. The integrated circuit structure of claim 11, wherein the intermediate dielectric layer has a dielectric constant less than the dielectric constant of the hardmask layer, and wherein the metal oxide layer has a dielectric constant greater than a dielectric constant of the intermediate dielectric layer.
15. The integrated circuit structure of claim 11, wherein the first low-k dielectric layer is a low-k

inter-layer dielectric layer.

16. The integrated circuit structure of claim 11, wherein the second low-k dielectric layer is a low-k inter-layer dielectric layer.

17. The integrated circuit structure of claim 11, wherein the first low-k dielectric layer is a first low-k inter-layer dielectric layer, wherein the second low-k dielectric layer is a second low-k inter-layer dielectric layer.

18. The integrated circuit structure of claim 11, wherein the conductive via includes a barrier layer comprising tantalum, and a conductive fill comprising copper.

19. The integrated circuit structure of claim 11, wherein the hardmask layer has a thickness in the range of 2-50 nm.

20. The integrated circuit structure of claim 11, wherein the hardmask layer further
