

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285945

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

TANIOKA; Tomonori et al.

SEMICONDUCTOR DEVICE INCLUDING A LEAD AND A SEALING RESIN

Abstract

There is provided a technique that includes: a lead having a main surface facing in a thickness direction; a semiconductor element mounted over the main surface; and a sealing resin that is in contact with the main surface and covers the semiconductor element, wherein the lead is formed with a plurality of grooves that are recessed from the main surface and are located apart from each other, and wherein the plurality of grooves are located away from a peripheral edge of the main surface.

Inventors: TANIOKA; Tomonori (Kyoto, JP), EGAMI; Kazuo (Kyoto, JP)

Applicant: ROHM CO., LTD. (Kyoto, JP)

Family ID: 84542583

Appl. No.: 19/211638

Filed: May 19, 2025

Foreign Application Priority Data

JP 2021-107705

Jun. 29, 2021

Related U.S. Application Data

parent US continuation 17831143 20220602 parent-grant-document US 12327780 child US 19211638

Publication Classification

Int. Cl.: H01L23/495 (20060101); H01L23/00 (20060101); H01L23/31 (20060101)

U.S. Cl.:

CPC **H01L23/49541** (20130101); **H01L23/3107** (20130101); **H01L23/49513** (20130101);
H01L23/562 (20130101); **H01L24/29** (20130101); H01L24/45 (20130101);
H01L2224/29111 (20130101); H01L2224/45124 (20130101); H01L2924/014 (20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION [0001] This application is a continuation application of U.S. application Ser. No. 17/831,143 filed Jun. 2, 2022 which is based upon and claims the benefit of priority from Japanese Patent Application No. 2021-107705, filed on Jun. 29, 2021, the entire contents of which are incorporated herein by reference.

TECHNICAL FIELD

[0002] The present disclosure relates to a semiconductor device including a lead and a sealing resin.

BACKGROUND

[0003] Patent Document 1 discloses an example of a semiconductor device including a first lead including a first pad having a pad main surface, a semiconductor element mounted on the pad main surface, and a sealing resin that is in contact with the pad main surface and covers the semiconductor element. The semiconductor element is conductively bonded to the first pad via a bonding layer. The semiconductor device further includes a second lead including a second pad and a wire (first bonding wire) conductively bonded to the semiconductor element and the second pad. The second pad and the wire are covered with the sealing resin. As a result, in the semiconductor device, the semiconductor element and members related to a conduction path of the semiconductor element are protected from external factors by the sealing resin.

[0004] When the semiconductor device disclosed in the related art is used, heat is generated from the semiconductor element. As a result, a thermal strain is generated in the first pad, so that a shear stress is generated at an interface between the pad main surface and the sealing resin. If the concentration of the shear stress becomes excessive, the sealing resin may peel off from the pad main surface and cracks may occur in the bonding layer interposed between the pad main surface and the semiconductor element. Further, due to the influence of heat conducted from the semiconductor element to the wire, a shear stress is also generated at a bonding interface between the second pad and the wire. This may cause pitting corrosion on the wire. Therefore, by improving the adhesion between the first pad/the second pad and the sealing resin, it is desired to prevent the sealing resin from peeling off and to prevent the bonding layer and the wire from being defective.

SUMMARY

[0005] Some embodiments of the present disclosure provide a semiconductor device capable of improving the adhesion between a lead and a sealing resin.

[0006] According to one embodiment of the present disclosure, there is provided a technique that includes: a lead having a main surface facing in a thickness direction; a semiconductor element mounted over the main surface; and a sealing resin that is in contact with the main surface and covers the semiconductor element, wherein the lead is formed with a plurality of grooves that are recessed from the main surface and are located apart from each other, and wherein the plurality of grooves are located away from a peripheral edge of the main surface.

[0007] Other features and advantages of the present disclosure will become more apparent with the detailed description given below based on the accompanying drawings.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0008] FIG. 1 is a perspective view of a semiconductor device according to a first embodiment of the present disclosure.

[0009] FIG. 2 is a plan view of the semiconductor device shown in FIG. 1.

[0010] FIG. 3 is a plan view corresponding to FIG. 2, which is transparent to a sealing resin.

[0011] FIG. 4 is a bottom view of the semiconductor device shown in FIG. 1.

[0012] FIG. 5 is a front view of the semiconductor device shown in FIG. 1.

[0013] FIG. 6 is a cross-sectional view taken along line VI-VI of FIG. 3.

[0014] FIG. 7 is a cross-sectional view taken along line VII-VII of FIG. 3.

[0015] FIG. 8 is a partially enlarged view of a semiconductor element shown in FIG. 3 and its vicinity thereof.

[0016] FIG. 9 is a partially enlarged view of a semiconductor device shown in FIG. 6 and its vicinity thereof.

[0017] FIG. 10 is a partially enlarged view of a cover portion of a terminal (first terminal) shown in FIG. 6 and its vicinity thereof.

[0018] FIG. 11 is a partially enlarged view of a lead shown in FIG. 3.

[0019] FIG. 12 is a cross-sectional view taken along line XII-XII of FIG. 11.

[0020] FIG. 13 is a partially enlarged plan view of a modification of the semiconductor device shown in FIG. 1, which is transparent to the sealing resin.

[0021] FIG. 14 is a partially enlarged plan view of a semiconductor device according to a second embodiment of the present disclosure, which is transparent to a sealing resin.

[0022] FIG. 15 is a partially enlarged plan view of a modification of the semiconductor device shown in FIG. 14, which is transparent to the sealing resin.

[0023] FIG. 16 is a partially enlarged plan view of a semiconductor device according to a third embodiment of the present disclosure, which is transparent to a sealing resin.

[0024] FIG. 17 is a partially enlarged plan view of a modification of the semiconductor device shown in FIG. 16, which is transparent to the sealing resin.

DETAILED DESCRIPTION

[0025] Embodiments for carrying out the present disclosure will now be described with reference to the accompanying drawings.

First Embodiment

[0026] A semiconductor device A10 according to a first embodiment of the present disclosure will be described with reference to FIGS. 1 to 12. The semiconductor device A10 is used for an electronic apparatus or the like including a power conversion circuit such as a DC-DC converter. The semiconductor device A10 includes a lead 10, a semiconductor element 30, a first bonding layer 39, a plurality of conductive members 40, and a sealing resin 50. Here, FIGS. 3, 8, and 11 are transparent to the sealing resin 50 for the sake of convenience of understanding. In FIG. 3, the sealing resin 50 is indicated by an imaginary line (two-dot chain line).

[0027] In the description of the semiconductor device A10, for the sake of convenience, a thickness direction of the lead 10 is referred to as a “thickness direction z.” A direction orthogonal to the thickness direction z is referred to as a “first direction x.” A direction orthogonal to both the thickness direction z and the first direction x is referred to as a “second direction y.” When viewed along the thickness direction z, the first direction x corresponds to a longitudinal direction (or long side direction) of the semiconductor device A10. When viewed along the thickness direction z, the second direction y corresponds to a lateral direction (or short side direction) of the semiconductor device A10.

[0028] As shown in FIGS. 3, 6, and 7, the lead 10 is a conductive member on which the

semiconductor element **30** is mounted and which forms a portion of a conduction path between the semiconductor element **30** and a wiring board on which the semiconductor device **A10** is mounted. In the semiconductor device **A10**, the lead **10** includes a die pad **11** and a plurality of terminals **12**, which are located apart from each other.

[0029] As shown in FIGS. **6** and **7**, the die pad **11** and the plurality of terminals **12** include a base material **101** and a metal layer **102**. The base material **101** forms a main part of the lead **10** and is obtained from the same lead frame. The lead frame is copper (Cu) or a copper alloy. Therefore, the composition of the base material **101** contains copper. The base material **101** has a main surface **101A** facing one side of the thickness direction *z*. The metal layer **102** is laminated on the main surface **101A**. A thickness of the metal layer **102** is thinner than a thickness of the base material **101**. The composition of the metal layer **102** includes silver (Ag). In addition, the composition of the metal layer **102** may include nickel (Ni).

[0030] As shown in FIGS. **3** and **7**, the die pad **11** has a pad portion **111** and a terminal portion **112**. The pad portion **111** includes the base material **101** and a first metal layer **102A**. The base material **101** of the pad portion **111** has a first main surface **111A**, a back surface **111B**, and a through-hole **111C**. The first main surface **111A** is included in the main surface **101A**. The back surface **111B** faces a side opposite to the first main surface **111A** in the thickness direction *z*. The back surface **111B** is plated with, for example, tin (Sn). The through-hole **111C** extends from the first main surface **111A** to the back surface **111B** in the thickness direction *z* and penetrates the pad portion **111**. The through-hole **111C** has a circular shape when viewed along the thickness direction *z*. The first metal layer **102A** is laminated on the first main surface **111A**. The first metal layer **102A** is included in the metal layer **102**. As shown in FIG. **6**, a thickness *T* of the base material **101** of the pad portion **111** is thicker than the maximum thickness *t.sub.max* of each base material **101** of the plurality of terminals **12**.

[0031] As shown in FIGS. **3** and **7**, the terminal portion **112** includes a portion extending along the first direction *x* and is connected to the base material **101** of the pad portion **111**. Therefore, the pad portion **111** and the terminal portion **112** are electrically connected to each other. A portion of the terminal portion **112** is covered with the sealing resin **50**. The portion of the terminal portion **112** covered with the sealing resin **50** is bent when viewed along the second direction *y*. A surface of the terminal portion **112** exposed from the sealing resin **50** is plated with tin.

[0032] As shown in FIGS. **3**, **6**, and **7**, the semiconductor element **30** is mounted over the first main surface **111A** of the pad portion **111** of the die pad **11**. In the semiconductor device **A10**, the semiconductor element **30** is an n-channel type MOSFET (Metal-Oxide-Semiconductor-Field-Effect-Transistor) having a vertical structure. The semiconductor element **30** includes a compound semiconductor substrate. A main material of the compound semiconductor substrate is silicon carbide (SiC). In addition, silicon (Si) may be used as the main material of the compound semiconductor substrate. In the semiconductor device **A10**, an area of the semiconductor element **30** is 40% or less of an area of the first main surface **111A** when viewed along the thickness direction *z*. The semiconductor element **30** is not limited to the MOSFET.

[0033] The semiconductor element **30** may be another transistor such as an IGBT (Insulated Gate Bipolar Transistor). Further, the semiconductor element **30** may be an LSI or a diode. The semiconductor element **30** includes a first electrode **31**, a second electrode **32**, and a third electrode **33**.

[0034] As shown in FIGS. **8** and **9**, the first electrode **31** is provided on a side facing the first main surface **111A** of the pad portion **111** of the die pad **11** in the thickness direction *z*. A current corresponding to power after being converted by the semiconductor element **30** flows through the first electrode **31**. That is, the first electrode **31** corresponds to a source of the semiconductor element **30**.

[0035] As shown in FIG. **9**, the second electrode **32** is provided on a side opposite to the first electrode **31** in the thickness direction *z*. The second electrode **32** faces the first main surface **111A**

of the pad portion **111** of the die pad **11**. A current corresponding to power before being converted by the semiconductor element **30** flows through the second electrode **32**. That is, the second electrode **32** corresponds to a drain of the semiconductor element **30**.

[0036] As shown in FIG. **8**, the third electrode **33** is provided on the same side as the first electrode **31** in the thickness direction z and is located away from the first electrode **31**. A gate voltage for driving the semiconductor element **30** is applied to the third electrode **33**. That is, the third electrode **33** corresponds to the gate of the semiconductor element **30**. An area of the third electrode **33** is smaller than an area of the first electrode **31** when viewed along the thickness direction z .

[0037] As shown in FIG. **9**, the first bonding layer **39** is interposed between the first main surface **111A** of the pad portion **111** of the die pad **11** and the second electrode **32** of the semiconductor element **30**. The first bonding layer **39** is in contact with the first metal layer **102A** of the pad portion **111**, and the second electrode **32**. The first bonding layer **39** is located on the first metal layer **102A**. The first bonding layer **39** contains a metal element. The metal element is, for example, tin. The first bonding layer **39** is, for example, solder. The second electrode **32** is conductively bonded to the pad portion **111** via the first bonding layer **39**. Therefore, the terminal portion **112** of the die pad **11** corresponds to a drain terminal of the semiconductor device **A10**.

[0038] As shown in FIG. **3**, the plurality of terminals **12** are electrically connected to the semiconductor element **30**. The plurality of terminals **12** have a cover portion **121** and an exposed portion **122**. The cover portion **121** is covered with the sealing resin **50**. The cover portion **121** includes the base material **101** and a second metal layer **102B**. The base material **101** of the cover portion **121** has a second main surface **121A**. The second main surface **121A** is included in the main surface **101A**. The second metal layer **102B** is laminated on the second main surface **121A**. The second metal layer **102B** is included in the metal layer **102**. When viewed along the thickness direction z , an area of the second metal layer **102B** is smaller than an area of the first metal layer **102A** of the pad portion **111** of the die pad **11**. The exposed portion **122** is connected to the base material **101** of the cover portion **121** and is exposed from the sealing resin **50**. The exposed portion **122** extends from the cover portion **121** to the side away from the pad portion **111** of the die pad **11** in the first direction x . The surface of the exposed portion **122** is plated with, for example, tin.

[0039] As shown in FIG. **3**, in the semiconductor device **A10**, the plurality of terminals **12** include a first terminal **12A** and a second terminal **12B**. The first terminal **12A** extends along the first direction x and is located next to the terminal portion **112** of the die pad **11** in the second direction y . The first terminal **12A** is electrically connected to the first electrode **31** of the semiconductor element **30**. Therefore, the first terminal **12A** corresponds to a source terminal of the semiconductor device **A10**.

[0040] As shown in FIG. **3**, the second terminal **12B** extends along the first direction x and is located on an opposite side of the first terminal **12A** with the terminal portion **112** of the die pad **11** sandwiched therebetween in the second direction y . The second terminal **12B** is electrically connected to the third electrode **33** of the semiconductor element **30**. Therefore, the second terminal **12B** corresponds to a gate terminal of the semiconductor device **A10**.

[0041] As shown in FIG. **5**, in the semiconductor device **A10**, the portion of the terminal portion **112** of the die pad **11** exposed from the sealing resin **50**, the exposed portion **122** of the first terminal **12A**, and the exposed portion **122** of the second terminal **12B** have a same height h . When viewed along the second direction y , a portion of the terminal portion **112** overlaps the exposed portion **122** of the first terminal **12A** and the exposed portion **122** of the second terminal **12B**.

[0042] As shown in FIGS. **3**, **11**, and **12**, a plurality of grooves **20** are formed in the lead **10** (the die pad **11** and the plurality of terminals **12**). The plurality of grooves **20** are recessed from the main surface **101A** (the first main surface **111A** and the second main surface **121A**) of the base material **101** and are located apart from each other. As shown in FIGS. **3**, **6**, and **7**, the plurality of grooves

20 are located apart from a peripheral edge **101B** of the main surface **101A**. The plurality of grooves **20** are formed by subjecting the main surface **101A** to laser machining. In FIG. 3, a portion of the lead **10** in which the plurality of grooves **20** are formed is indicated by a region of a plurality of straight lines.

[0043] As shown in FIG. 11, the plurality of grooves **20** include a plurality of first grooves **21** and a plurality of second grooves **22**. The plurality of first grooves **21** and the plurality of second grooves **22** are arranged along the first direction x . The plurality of first grooves **21** and the plurality of second grooves **22** have a linear shape extending in a direction orthogonal to the thickness direction z . As a result, the plurality of first grooves **21** and the plurality of second grooves **22** form a broken line when viewed along the thickness direction z . In FIG. 11, the plurality of second grooves **22** are indicated by a region of a plurality of points.

[0044] As shown in FIG. 11, in the semiconductor device **A10**, the plurality of first grooves **21** and the plurality of second grooves **22** extend in the first direction x . The plurality of second grooves **22** are located next to the plurality of first grooves **21** in the second direction y . In the first direction x , at least a portion of any one of the plurality of second grooves **22** is located between two adjacent first grooves **21** in the first direction x among the plurality of first grooves **21**. A length $L2$ of each of the plurality of second grooves **22** is longer than a length $L1$ of each of the plurality of first grooves **21**.

[0045] As shown in FIG. 3, in the pad portion **111** of the die pad **11** of the lead **10**, the plurality of grooves **20** surround the first bonding layer **39** and the first metal layer **102A** when viewed along the thickness direction z . Further, in the cover portion **121** of the plurality of terminals **12** of the lead **10**, the plurality of grooves **20** surround the second metal layer **102B** when viewed along the thickness direction z .

[0046] As shown in FIG. 3, the plurality of conductive members **40** are conductively bonded to the semiconductor element **30** and the plurality of terminals **12**. As a result, mutual conduction between the semiconductor element **30** and the plurality of terminals **12** is achieved. The plurality of conductive members **40** include a first member **41** and a second member **42**.

[0047] As shown in FIGS. 3, 9, and 10, the first member **41** is conductively bonded to the first electrode **31** of the semiconductor element **30** and the second metal layer **102B** of the cover portion **121** of the first terminal **12A**. As a result, the first terminal **12A** is electrically connected to the first electrode **31**. The composition of the first member **41** includes copper. In the semiconductor device **A10**, the first member **41** is a metal clip. The first member **41** is conductively bonded to the first electrode **31** and the second metal layer **102B** via a second bonding layer **49**. The second bonding layer **49** contains a metal element. The metal element is, for example, tin. The second bonding layer **49** is, for example, solder. As shown in FIG. 9, a thickness $t2$ of the second bonding layer **49** is smaller than a thickness $t1$ of the first bonding layer **39**. In addition, the first member **41** may be a wire. In this case, since the first member **41** is formed by wire bonding, the second bonding layer **49** becomes unnecessary.

[0048] As shown in FIGS. 3 and 8, the second member **42** is conductively bonded to the third electrode **33** of the semiconductor element **30** and the second metal layer **102B** of the cover portion **121** of the second terminal **12B**. As a result, the second terminal **12B** is electrically connected to the third electrode **33**. The second member **42** is a wire. The second member **42** is formed by wire bonding. The composition of the second member **42** includes aluminum (Al).

[0049] The differences between the first member **41** and the second member **42** will be described below. The Young's modulus (elastic modulus) of the second member **42** is smaller than the Young's modulus of the first member **41**. This is based on the fact that, as described above, the composition of the first member **41** includes copper and the composition of the second member **42** includes aluminum. Therefore, a linear expansion coefficient of the second member **42** is larger than a linear expansion coefficient of the first member **41**. In addition, a thermal conductivity of the second member **42** is smaller than a thermal conductivity of the first member **41**. Further, as shown

in FIG. 8, a width B of the first member **41** is larger than a width (diameter) D of the second member **42**.

[0050] As shown in FIGS. 6 and 7, the sealing resin **50** covers the semiconductor element **30**, the plurality of conductive members **40**, and a portion of each of the die pad **11** and the plurality of terminals **12**. The sealing resin **50** is in contact with the main surface **101A** of the base material **101** of the lead **10**. The sealing resin **50** has electrical insulation. The sealing resin **50** is made of a material including, for example, a black epoxy resin. The sealing resin **50** has a top surface **51**, a bottom surface **52**, a pair of first side surfaces **53**, a pair of second side surfaces **54**, a pair of openings **55**, and a mounting hole **56**.

[0051] As shown in FIGS. 6 and 7, the top surface **51** faces the same side as the first main surface **111A** of the pad portion **111** of the die pad **11** in the thickness direction z. As shown in FIGS. 5 to 7, the bottom surface **52** faces a side opposite to the top surface **51** in the thickness direction z. The back surface **111B** of the pad portion **111** is exposed from the bottom surface **52**.

[0052] As shown in FIGS. 2 and 4, the pair of first side surfaces **53** are located apart from each other in the first direction x. The pair of first side surfaces **53** are connected to the top surface **51** and the bottom surface **52**. As shown in FIG. 5, a portion of the terminal portion **112** of the die pad **11** and the exposed portion **122** of the first terminal **12A** and the second terminal **12B** are exposed from one of the pair of first side surfaces **53**.

[0053] As shown in FIGS. 2, 4, and 5, the pair of second side surfaces **54** are located apart from each other in the second direction y. The pair of second side surfaces **54** are connected to the top surface **51** and the bottom surface **52**. As shown in FIG. 2, the pair of openings **55** are located apart from each other in the second direction y. Each of the pair of openings **55** is recessed toward inward side of the sealing resin **50** from the top surface **51** and any one of the pair of second side surfaces **54**. The first main surface **111A** of the pad portion **111** of the die pad **11** is exposed from the pair of openings **55**. As shown in FIGS. 2, 4, and 7, the mounting hole **56** extends from the top surface **51** to the bottom surface **52** in the thickness direction z and penetrates the sealing resin **50**. When viewed along the thickness direction z, the mounting hole **56** is included in the through-hole **111C** of the pad portion **111** of the die pad **11**. An inner peripheral surface of the pad portion **111** that defines the through-hole **111C** is covered with the sealing resin **50**. As a result, the maximum dimension of the mounting hole **56** is smaller than the dimension of the through-hole **111C** when viewed along the thickness direction z.

Modification of the First Embodiment

[0054] Next, a semiconductor device **A11**, which is a modification of the semiconductor device **A10**, will be described with reference to FIG. 13. Here, the position of FIG. 13 is the same as the position of FIG. 11. Similar to FIG. 11, FIG. 13 is transparent to the sealing resin **50**, and the plurality of second grooves **22** are indicated by a region of a plurality of points.

[0055] The semiconductor device **A11** is different from the semiconductor device **A10** in the configuration of the plurality of second grooves **22** among the plurality of grooves **20**. As shown in FIG. 13, when viewed along the second direction y, both sides of any of the plurality of second grooves **22** in the first direction x overlap with two adjacent first grooves **21** in the first direction x among the plurality of first grooves **21**. This configuration is obtained by setting a length L2 of each of the plurality of second grooves **22** to be longer than a length L2 in the case of the semiconductor device **A10**.

[0056] Next, the operation and effects of the semiconductor device **A10** will be described.

[0057] The semiconductor device **A10** includes the lead **10** having the main surface **101A**, the semiconductor element **30** mounted over the main surface **101A**, and the sealing resin **50** that is in contact with the main surface **101A** and covers the semiconductor element **30**. The lead **10** is formed with the plurality of grooves **20** that are recessed from the main surface **101A** and are located apart from each other. The plurality of grooves **20** are located apart from a peripheral edge **101B** of the main surface **101A**. As a result, when the sealing resin **50** is in contact with the main

surface **101A** is inserted into the plurality of grooves **20**, the sealing resin **50** exhibits an anchoring effect. As a result, a bonding strength of the sealing resin **50** with respect to the main surface **101A** increases. Therefore, according to the semiconductor device **A10**, it is possible to improve the adhesion between the lead **10** and the sealing resin **50**.

[0058] The plurality of grooves **20** include the plurality of first grooves **21** and the plurality of second grooves **22** arranged along the first direction **x**. The plurality of first grooves **21** and the plurality of second grooves **22** have a linear shape extending in a direction orthogonal to the thickness direction **z**. As a result, since the plurality of first grooves **21** and the plurality of second grooves **22** form a broken line, the extension of the plurality of grooves **20** per unit area of the main surface **101A** of the lead **10** can be shortened. Therefore, according to the semiconductor device **A10**, it is possible to shorten the laser machining time for forming the plurality of grooves **20** while improving the adhesion between the lead **10** and the sealing resin **50**.

[0059] In the semiconductor device **A10**, the plurality of second grooves **22** are located next to the plurality of first grooves **21** in the second direction **y**. The plurality of first grooves **21** and the plurality of second grooves **22** extend in the first direction **x**. In the first direction **x**, at least a portion of any of the plurality of second grooves **22** is located between two adjacent first grooves **21** among the plurality of first grooves **21**. As a result, the plurality of grooves **20** can resist a shear stress, which is delivered to the interface between the main surface **101A** of the lead **10** and the sealing resin **50**, from multiple directions. Therefore, it is possible to further increase a bonding strength of the sealing resin **50** with respect to the main surface **101A** while shortening the laser machining time for forming the plurality of grooves **20**.

[0060] In the semiconductor device **All**, when viewed along the second direction **y**, both sides of one of the plurality of second grooves **22** in the first direction **x** overlap with two adjacent first grooves **21** among the plurality of first grooves **21**. As a result, the plurality of grooves **20** can more strongly resist the shear stress delivered in the second direction **y** to the interface between the main surface **101A** of the lead **10** and the sealing resin **50**.

[0061] The semiconductor device **A10** further includes the conductive member **40** (the first member **41**) conductively bonded to the first electrode **31** of the semiconductor element **30** and the terminal **12** (the first terminal **12A**) which is one element of the lead **10**. The terminal **12** includes the base material **101** having the second main surface **121A**, and the metal layer **102** (the second metal layer **102B**) laminated on the second main surface **121A**. The second main surface **121A** is included in the main surface **101A** where the plurality of grooves **20** are to be formed. The conductive member **40** is conductively bonded to the metal layer **102**. When the adhesion between the base material **101** of the terminal **12** and the sealing resin **50** is improved with the formation of the plurality of grooves **20**, the shear stress delivered to the bonding interface between the metal layer **102** and the conductive member **40** can be reduced. Therefore, it is possible to prevent the occurrence of pitting corrosion of the conductive member **40**. Further, when the conductive member **40** is conductively bonded to the metal layer **102** in the manufacture of the semiconductor device **A10**, the metal layer **102** has an effect of reducing an impact caused by the conduction bonding, which is delivered to the base material **101**.

[0062] The semiconductor device **A10** further includes a bonding layer (the first bonding layer **39**) interposed between the first main surface **111A** of the die pad **11** (the pad portion **111**) and the semiconductor element **30**. The die pad **11** is an element of the lead **10**. The first main surface **111A** is included in the main surface **101A** where the plurality of grooves **20** are to be formed. When the adhesion between the die pad **11** and the sealing resin **50** is improved with the formation of the plurality of grooves **20**, the shear stress delivered to the interface between the first main surface **111A** and the sealing resin **50** is less likely to reach the bonding layer. This makes it possible to prevent the occurrence of cracks in the bonding layer.

[0063] In the above case, it is preferable that the plurality of grooves **20** surround the bonding layer when viewed along the thickness direction **z**. As a result, the shear stress reaching the bonding layer

from the interface between the first main surface **111A** of the die pad **11** and the sealing resin **50** can be effectively reduced. Further, in the manufacture of the semiconductor device **A10**, when the semiconductor element **30** is bonded to the die pad **11**, the bonding layer melted by reflow (when the bonding layer is solder) can be prevented by the plurality of grooves **20** from being excessively wetted and spreading on the first main surface **111A**. This makes it possible to prevent short-circuit between the die pad **11** and the terminal **12** due to the bonding layer adhered to the terminal **12**. Further, it is possible to suppress a positional deviation of the semiconductor element **30** with respect to the first main surface **111A** due to the molten bonding layer.

[0064] When viewed along the thickness direction z , the plurality of grooves **20** surround the first metal layer **102A** laminated on the first main surface **111A** of the die pad **11**. The bonding layer is located on the first metal layer **102A**. As a result, in the manufacture of the semiconductor device **A10**, when the semiconductor element **30** is bonded to the die pad **11**, it is possible to prevent the bonding layer from being wetted and spreading on the first main surface **111A** while improving the wettability of the bonding layer (when the bonding layer is solder) with respect to the die pad **11**.

[0065] The thickness t_1 of the first bonding layer **39** is larger than the thickness t_2 of the second bonding layer **49**. As a result, when the semiconductor device **A10** is used, heat generated from the semiconductor element **30** is likely to be conducted to the die pad **11** having a larger volume than each of the plurality of conductive members **40**. This makes it possible to improve heat dissipation of the semiconductor device **A10**.

[0066] The composition of the base material **101** of the lead **10** includes copper. Further, the thickness T of the base material **101** of the pad portion **111** of the die pad **11** is larger than the maximum thickness $t_{\text{sub.max}}$ of the terminal **12**. As a result, it is possible to increase efficiency of heat conduction in the direction orthogonal to the thickness direction z while improving heat conductivity of the pad portion **111**. This contributes to the improvement of heat dissipation of the die pad **11**.

[0067] The base material **101** of the pad portion **111** has the back surface **111B** facing a side opposite to the first main surface **111A** in the thickness direction z . The back surface **111B** is exposed from the bottom surface **52** of the sealing resin **50**. As a result, while the sealing resin **50** protects the semiconductor element **30** and the conductive member **40** from external factors, it is possible to avoid a decrease in heat dissipation of the semiconductor device **A10**.

Second Embodiment

[0068] A semiconductor device **A20** according to a second embodiment of the present disclosure will be described with reference to FIG. **14**. In this figure, the same or similar elements of the above-described semiconductor device **A10** are denoted by the same reference numerals, and explanation thereof will not be repeated. Here, the position of FIG. **14** is the same as the position of FIG. **11** showing the semiconductor device **A10**. Similar to FIG. **11**, FIG. **14** is transparent to the sealing resin **50**, and the plurality of second grooves **22** are indicated by a region of a plurality of points.

[0069] The semiconductor device **A20** is different from the above-described semiconductor device **A10** in the configuration of the plurality of grooves **20**.

[0070] As shown in FIG. **14**, the plurality of first grooves **21** extend in the first direction x . The plurality of second grooves **22** extend in the second direction y . When viewed along the second direction y , any of the plurality of second grooves **22** overlaps with any of the plurality of first grooves **21**. A length L_2 of each of the plurality of second grooves **22** is shorter than a length L_1 of each of the plurality of first grooves **21**.

Modification of the Second Embodiment

[0071] Next, a semiconductor device **A21**, which is a modification of the semiconductor device **A20**, will be described with reference to FIG. **15**. Here, the position of FIG. **15** is the same as the position of FIG. **14**. Similar to FIG. **14**, FIG. **15** is transparent to the sealing resin **50**, and the plurality of second grooves **22** are indicated by a region of a plurality of points.

[0072] The semiconductor device A21 is different from the semiconductor device A20 in the configuration of the plurality of second grooves 22 among the plurality of grooves 20. As shown in FIG. 15, in the first direction x, any of the plurality of second grooves 22 is located between two adjacent first grooves 21 in the first direction x among the plurality of first grooves 21.

[0073] Next, the operation and effects of the semiconductor device A20 will be described.

[0074] The semiconductor device A20 includes the lead 10 having the main surface 101A, the semiconductor element 30 mounted over the main surface 101A, and the sealing resin 50 that is in contact with the main surface 101A and covers the semiconductor element 30. The lead 10 is formed with the plurality of grooves 20 that are recessed from the main surface 101A and are located apart from each other. The plurality of grooves 20 are located apart from the peripheral edge 101B of the main surface 101A. Therefore, the semiconductor device A20 can also improve the adhesion between the lead 10 and the sealing resin 50.

[0075] Also in the semiconductor device A20, the plurality of grooves 20 include the plurality of first grooves 21 and the plurality of second grooves 22 arranged along the first direction x. The plurality of first grooves 21 and the plurality of second grooves 22 have a linear shape extending in a direction orthogonal to the thickness direction z. Therefore, the semiconductor device A20 also makes it possible to shorten the laser machining time for forming the plurality of grooves 20 while improving the adhesion between the lead 10 and the sealing resin 50.

[0076] In the semiconductor device A20, the plurality of second grooves 22 are located next to the plurality of first grooves 21 in the second direction y. The plurality of first grooves 21 extend in the first direction x. The plurality of second grooves 22 extend in the second direction y. As a result, the plurality of grooves 20 can resist the shear stress, which is delivered to the interface between the main surface 101A of the lead 10 and the sealing resin 50, from multiple directions. Further, the extension of the plurality of grooves 20 per unit area of the main surface 101A can be shortened as compared with the case of the semiconductor device A10. Therefore, according to the semiconductor device A20, it is possible to further increase a bonding strength of the sealing resin 50 with respect to the main surface 101A while further shortening a laser machining time for forming the plurality of grooves 20.

[0077] In the semiconductor device A21, in the first direction x, any one of the plurality of second grooves 22 is located between two adjacent first grooves 21 among the plurality of first grooves 21. As a result, a distance between the two adjacent first grooves 21 in the first direction x among the plurality of first grooves 21 can be set longer. Therefore, the extension of the plurality of grooves 20 per unit area of the main surface 101A of the lead 10 can be further shortened as compared with the case of the semiconductor device A20.

[0078] In the semiconductor device A20, a length L2 of each of the plurality of second grooves 22 is shorter than a length L1 of each of the plurality of first grooves 21. With this configuration, it is possible to prevent the distance between the two adjacent first grooves 21 in the second direction y among the plurality of first grooves 21 from being excessively widened. As a result, it is possible to ensure an increase of a bonding strength of the lead 10 with respect to the main surface 101A.

[0079] Further, when the semiconductor device A20 has the same configuration as the semiconductor device A10, the semiconductor device A20 also exerts the operation and effects related to the configuration.

Third Embodiment

[0080] A semiconductor device A30 according to a third embodiment of the present disclosure will be described with reference to FIG. 16. In this figure, the same or similar elements of the above-described semiconductor device A10 are denoted by the same reference numerals, and explanation thereof will not be repeated. Here, the position of FIG. 16 is the same as the position of FIG. 11 showing the semiconductor device A10. Similar to FIG. 11, FIG. 16 is transparent to the sealing resin 50, and the plurality of second grooves 22 are indicated by a region of a plurality of points.

[0081] The semiconductor device A30 is different from the above-described semiconductor device

A10 in the configuration of the plurality of grooves **20**.

[0082] As shown in FIG. **16**, the plurality of first grooves **21** extend in the first direction **x**. The plurality of second grooves **22** extend in the second direction **y**. One of the plurality of second grooves **22** is located between two adjacent first grooves **21** among the plurality of first grooves **21**.

Modification of the Third Embodiment

[0083] Next, a semiconductor device **A31**, which is a modification of the semiconductor device **A30**, will be described with reference to FIG. **17**. Here, the position of FIG. **17** is the same as the position of FIG. **16**. Similar to FIG. **16**, FIG. **17** is transparent to the sealing resin **50**, and the plurality of second grooves **22** are indicated by a region of a plurality of points.

[0084] The semiconductor device **A31** is different from the semiconductor device **A30** in the configuration of the plurality of grooves **20**. As shown in FIG. **17**, the plurality of grooves **20** include a plurality of third grooves **23**. The plurality of third grooves **23** are arranged along the first direction **x** and are located next to the plurality of first grooves **21** in the second direction **y**. The plurality of third grooves **23** extend in the first direction **x**. One of the plurality of second grooves **22** is located between two adjacent third grooves **23** in the first direction **x** among the plurality of third grooves **23**. That is, both sides of any of the plurality of second grooves **22** in the second direction **y** are sandwiched between two first grooves **21** adjacent to each other in the first direction **x** and two adjacent third grooves **23** in the first direction **x**.

[0085] Next, the operation and effects of the semiconductor device **A30** will be described.

[0086] The semiconductor device **A30** includes the lead **10** having the main surface **101A**, the semiconductor element **30** mounted over the main surface **101A**, and the sealing resin **50** that is in contact with the main surface **101A** and covers the semiconductor element **30**. The lead **10** is formed with the plurality of grooves **20** that are recessed from the main surface **101A** and are located apart from each other. The plurality of grooves **20** are located apart from the peripheral edge **101B** of the main surface **101A**. Therefore, the semiconductor device **A30** can also improve the adhesion between the lead **10** and the sealing resin **50**.

[0087] Also in the semiconductor device **A30**, the plurality of grooves **20** include the plurality of first grooves **21** and the plurality of second grooves **22** arranged along the first direction **x**. The plurality of first grooves **21** and the plurality of second grooves **22** have a linear shape extending in a direction orthogonal to the thickness direction **z**. Therefore, the semiconductor device **A30** can also shorten the laser machining time for forming the plurality of grooves **20** while improving the adhesion between the lead **10** and the sealing resin **50**.

[0088] In the semiconductor device **A30**, the plurality of first grooves **21** extend in the first direction **x**. The plurality of second grooves **22** extend in the second direction **y**. One of the plurality of second grooves **22** is located between two adjacent first grooves **21** among the plurality of first grooves **21**. As a result, the plurality of grooves **20** can resist the shear stress, which is delivered to the interface between the main surface **101A** of the lead **10** and the sealing resin **50**, from multiple directions. Further, the extension of the plurality of grooves **20** per unit area of the main surface **101A** can be shortened as compared with the case of the semiconductor device **A10**. Therefore, according to the semiconductor device **A30**, it is possible to further increase a bonding strength of the sealing resin **50** with respect to the main surface **101A** while further shortening the laser machining time for forming the plurality of grooves **20**.

[0089] In the semiconductor device **A31**, the plurality of grooves **20** include the plurality of third grooves **23** arranged along the first direction **x** and located next to the plurality of first grooves **21** in the second direction **y**. The plurality of third grooves **23** extend in the first direction **x**. One of the plurality of second grooves **22** is located between two adjacent third grooves **23** among the plurality of third grooves **23**. As a result, the plurality of grooves **20** can more strongly resist the shear stress in the first direction **x**, which is delivered to the interface between the main surface **101A** of the lead **10** and the sealing resin **50**.

[0090] Further, when the semiconductor device **A30** has the same configuration as the

semiconductor device A10, the semiconductor device A30 also exerts the operation and effects related to the configuration.

[0091] The present disclosure is not limited to the above-described embodiments. The specific configuration of each part of the present disclosure can be freely changed in design.

[0092] The technical configurations of the semiconductor device provided by the present disclosure and the method for manufacturing the semiconductor device are described below.

Supplementary Note 1

[0093] A semiconductor device including: [0094] a lead having a main surface facing in a thickness direction; [0095] a semiconductor element mounted over the main surface; and [0096] a sealing resin that is in contact with the main surface and covers the semiconductor element, [0097] wherein the lead is formed with a plurality of grooves that are recessed from the main surface and are located apart from each other, and [0098] wherein the plurality of grooves are located away from a peripheral edge of the main surface.

Supplementary Note 2

[0099] The semiconductor device of Supplementary Note 1, wherein the plurality of grooves include a plurality of first grooves and a plurality of second grooves arranged along a first direction which is a direction orthogonal to the thickness direction, and [0100] wherein the plurality of first grooves and the plurality of second grooves are linear shapes extending in a direction orthogonal to the thickness direction.

Supplementary Note 3

[0101] The semiconductor device of Supplementary Note 2, wherein the plurality of second grooves are located next to the plurality of first grooves in a second direction orthogonal to the thickness direction and the first direction.

Supplementary Note 4

[0102] The semiconductor device of Supplementary Note 3, wherein the plurality of first grooves and the plurality of second grooves extend in the first direction, and [0103] wherein, in the first direction, at least a portion of any of the plurality of second grooves is located between two adjacent first grooves among the plurality of first grooves. [0104] Supplementary Note 5

[0105] The semiconductor device of Supplementary Note 4, wherein, when viewed along the second direction, both sides of any of the plurality of second grooves in the first direction overlap with the two adjacent first grooves among the plurality of first grooves.

Supplementary Note 6

[0106] The semiconductor device of Supplementary Note 4 or 5, wherein a length of each of the plurality of second grooves is longer than a length of each of the plurality of first grooves.

Supplementary Note 7

[0107] The semiconductor device of Supplementary Note 3, wherein the plurality of first grooves extend in the first direction, and [0108] wherein the plurality of second grooves extend in the second direction.

Supplementary Note 8

[0109] The semiconductor device of Supplementary Note 7, wherein, in the first direction, any of the plurality of second grooves is located between two adjacent first grooves among the plurality of first grooves.

Supplementary Note 9

[0110] The semiconductor device of Supplementary Note 7 or 8, wherein a length of each of the plurality of second grooves is shorter than a length of each of the plurality of first grooves.

Supplementary Note 10

[0111] The semiconductor device of Supplementary Note 2, wherein the plurality of first grooves extend in the first direction, [0112] wherein the plurality of second grooves extend in a second direction orthogonal to the thickness direction and the first direction, and [0113] wherein any of the plurality of second grooves is located between two adjacent first grooves among the plurality of

first grooves.

Supplementary Note 11

[0114] The semiconductor device of Supplementary Note 10, wherein the plurality of grooves further include a plurality of third grooves arranged along the first direction and located next to the plurality of first grooves in the second direction, [0115] wherein the plurality of third grooves extend in the first direction, and [0116] wherein any of the plurality of second grooves is located between two adjacent third grooves among the plurality of third grooves.

Supplementary Note 12

[0117] The semiconductor device of any one of Supplementary Notes 1 to 11, wherein the lead includes a die pad and a terminal located apart from each other, [0118] wherein the main surface includes a first main surface included in the die pad and a second main surface included in the terminal, [0119] wherein the semiconductor element is mounted over the first main surface, and [0120] wherein the terminal is electrically connected to the semiconductor element.

Supplementary Note 13

[0121] The semiconductor device of Supplementary Note 12, wherein the semiconductor element includes a first electrode provided on a side facing the first main surface in the thickness direction, and [0122] wherein the semiconductor device further includes a conductive member conductively bonded to the first electrode and the terminal.

Supplementary Note 14

[0123] The semiconductor device of Supplementary Note 13, wherein the terminal includes a base material having the second main surface, and a metal layer laminated on the second main surface, and [0124] wherein the conductive member is conductively bonded to the metal layer.

Supplementary Note 15

[0125] The semiconductor device of Supplementary Note 13 or 14, further including a bonding layer interposed between the first main surface and the semiconductor element, [0126] wherein the bonding layer contains a metal element.

Supplementary Note 16

[0127] The semiconductor device of Supplementary Note 15, wherein the semiconductor element includes a second electrode provided on a side opposite to the first electrode in the thickness direction, and [0128] wherein the second electrode is conductively bonded to the die pad via the bonding layer.

Supplementary Note 17

[0129] The semiconductor device of Supplementary Note 15 or 16, wherein the plurality of grooves surround the bonding layer when viewed along the thickness direction.

[0130] According to the present disclosure in some embodiments, it is possible to provide a semiconductor device capable of improving adhesion between a lead and a sealing resin.

[0131] While certain embodiments have been described, these embodiments have been presented by way of example only, and are not intended to limit the scope of the disclosures. Indeed, the embodiments described herein may be embodied in a variety of other forms. Furthermore, various omissions, substitutions and changes in the form of the embodiments described herein may be made without departing from the spirit of the disclosures. The accompanying claims and their equivalents are intended to cover such forms or modifications as would fall within the scope and spirit of the disclosures.

Claims

1. A semiconductor device comprising: a lead having a main surface facing in a thickness direction; a semiconductor element mounted over the main surface; and a sealing resin that is in contact with the main surface and covers the semiconductor element, wherein the lead is formed with a plurality of grooves that are recessed from the main surface and are located apart from each other, wherein

the plurality of grooves are located away from a peripheral edge of the main surface, wherein the plurality of grooves include a plurality of first grooves and a plurality of second grooves arranged along a first direction which is a direction orthogonal to the thickness direction, wherein the plurality of first grooves and the plurality of second grooves are linear shapes extending in a direction orthogonal to the thickness direction, and wherein along a second direction orthogonal to the thickness direction and the first direction, at least two of the plurality of first grooves and at least two of the plurality of second grooves are alternately arranged.

2. The semiconductor device of claim 1, wherein the plurality of first grooves and the plurality of second grooves extend in the first direction, and wherein, along the first direction, at least a portion of any of the plurality of second grooves is located between two adjacent first grooves among the plurality of first grooves.

3. The semiconductor device of claim 2, wherein, when viewed along the second direction, both sides of any of the plurality of second grooves in the first direction overlap with two adjacent first grooves among the plurality of first grooves.

4. The semiconductor device of claim 2, wherein a length of each of the plurality of second grooves is longer than a length of each of the plurality of first grooves.

5. The semiconductor device of claim 1, wherein the plurality of first grooves extend in the first direction, and wherein the plurality of second grooves extend in the second direction.

6. The semiconductor device of claim 5, wherein, along the first direction, any of the plurality of second grooves is located between two adjacent first grooves among the plurality of first grooves.

7. The semiconductor device of claim 5, wherein a length of each of the plurality of second grooves is shorter than a length of each of the plurality of first grooves.

8. The semiconductor device of claim 1, wherein the plurality of first grooves extend in the first direction, wherein the plurality of second grooves extend in the second direction, and wherein any of the plurality of second grooves is located between two adjacent first grooves among the plurality of first grooves.

9. The semiconductor device of claim 1, wherein the lead includes a die pad and a terminal located apart from each other, wherein the main surface includes a first main surface included in the die pad and a second main surface included in the terminal, wherein the semiconductor element is mounted over the first main surface, and wherein the terminal is electrically connected to the semiconductor element.

10. The semiconductor device of claim 9, wherein the semiconductor element includes a first electrode provided on a side facing the first main surface in the thickness direction, and wherein the semiconductor device further comprises a conductive member conductively bonded to the first electrode and the terminal.

11. The semiconductor device of claim 10, wherein the terminal includes a base material having the second main surface, and a metal layer laminated on the second main surface, and wherein the conductive member is conductively bonded to the metal layer.

12. The semiconductor device of claim 10, further comprising a bonding layer interposed between the first main surface and the semiconductor element, wherein the bonding layer contains a metal element.

13. The semiconductor device of claim 12, wherein the semiconductor element includes a second electrode provided on a side opposite to the first electrode in the thickness direction, and wherein the second electrode is conductively bonded to the die pad via the bonding layer.

14. The semiconductor device of claim 12, wherein the plurality of grooves surround the bonding layer when viewed along the thickness direction.
