

(12) **United States Patent**
Liu et al.

(10) **Patent No.:** **US 12,414,330 B2**
(45) **Date of Patent:** **Sep. 9, 2025**

(54) **MULTI-GATE DEVICE INCLUDING SEMICONDUCTOR FIN BETWEEN DIELECTRIC FINES AND METHOD OF FABRICATION THEREOF**

H01L 29/0673; H01L 29/0847; H01L 29/165; H01L 29/267; H01L 29/42392; H01L 29/66439; H01L 29/66545; H01L 29/6656; H01L 29/66772; H01L 29/775; H01L 29/7848; H01L 29/78645;
(Continued)

(71) Applicant: **TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.**, Hsinchu (TW)

(56) **References Cited**

(72) Inventors: **Ko-Cheng Liu**, Hsinchu (TW); **Chang-Miao Liu**, Hsinchu (TW); **Huiling Shang**, Hsinchu Country (TW)

U.S. PATENT DOCUMENTS

(73) Assignee: **TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.**, Hsinchu (TW)

8,772,109 B2 7/2014 Colinge
8,785,285 B2 7/2014 Tsai et al.
(Continued)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 497 days.

FOREIGN PATENT DOCUMENTS

TW 202147436 A 12/2021

Primary Examiner — Cheung Lee

(74) *Attorney, Agent, or Firm* — HAYNES AND BOONE, LLP

(21) Appl. No.: **17/832,651**

(22) Filed: **Jun. 5, 2022**

(65) **Prior Publication Data**

US 2023/0395681 A1 Dec. 7, 2023

(51) **Int. Cl.**
H10D 30/67 (2025.01)
H10D 62/10 (2025.01)
(Continued)


(52) **U.S. Cl.**
CPC **H10D 30/6735** (2025.01); **H10D 30/6733** (2025.01); **H10D 30/6757** (2025.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 21/823412; H01L 21/823431; H01L 21/823468; H01L 21/823481; H01L 27/088; H01L 27/0886; H01L 29/0649;

(57) **ABSTRACT**

A method includes forming a semiconductor fin protruding from a substrate, forming a cladding layer on sidewalls of the semiconductor fin, forming first and second dielectric fins sandwiching the semiconductor fin, and removing the cladding layer. The removal of the cladding layer forms trenches between the semiconductor fin and the first and second dielectric fins. After the removing of the cladding layer, a dummy gate structure is formed over the semiconductor fin and in the trenches. The method also includes recessing the semiconductor fin in a region proximal to the dummy gate structure, forming an epitaxial feature on the recessed semiconductor fin, and forming a metal gate stack replacing the dummy gate structure. A top surface of the recessed semiconductor fin in the region has a concave shape.

20 Claims, 44 Drawing Sheets



- (51) **Int. Cl.**
H10D 64/01 (2025.01)
H10D 84/01 (2025.01)
H10D 84/03 (2025.01)
- (52) **U.S. Cl.**
 CPC *H10D 62/115* (2025.01); *H10D 64/017*
 (2025.01); *H10D 64/021* (2025.01); *H10D*
84/0128 (2025.01); *H10D 84/0147* (2025.01);
H10D 84/0151 (2025.01); *H10D 84/0158*
 (2025.01); *H10D 84/038* (2025.01)
- (58) **Field of Classification Search**
 CPC H01L 29/78696; H10D 30/0273; H10D
 30/501–509; H10D 30/6735; H10D
 62/115; H10D 64/017
 See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,816,444	B2	8/2014	Wann et al.
8,823,065	B2	9/2014	Wang et al.
8,860,148	B2	10/2014	Hu et al.
9,105,490	B2	8/2015	Wang et al.
9,236,267	B2	1/2016	De et al.
9,236,300	B2	1/2016	Liaw
9,520,482	B1	12/2016	Chang et al.
9,576,814	B2	2/2017	Wu et al.
2019/0122934	A1	4/2019	Chang et al.
2020/0294859	A1	9/2020	Chang et al.
2021/0091179	A1 *	3/2021	Wang H01L 29/66469
2021/0098304	A1 *	4/2021	Chang H01L 29/66553
2021/0257480	A1 *	8/2021	Jhan H01L 29/66545

* cited by examiner




Fig. 1A




Fig. 1B




Fig. 2A




Fig. 2B




Fig. 3B






Fig. 3A






Fig. 5B




Fig. 5A




Fig. 6B




Fig. 6A




Fig. 7A






Fig. 7B


$$\begin{array}{c} \infty \\ \text{Fi}^* \end{array}$$


8A
E. 50




Fig. 9A




Fig. 9B




Fig. 9D

Fig. 9C




Fig. 10A





Fig. 10B

Li⁵⁰ 10D

Fi 50 100




Fig. 10F

Fig. 10E




Fig. 11A




Fig. 11B





Fig. 11D

Fig. 11C



1150

FILE




Fig. 12A




Fig. 12B




Fig. 12D

Fig. 12C




Fig. 12F

Fig. 12E





Fig. 13A

13B
Fi 00*


13.00
L. 1.00

Fig. 130




Fig. 13F

Fig. 13E




Fig. 14A





Fig. 14B



1960

Fig. 140




Fig. 14F

Fig. 14E




Fig. 15A




Fig. 15B





Fig. 15D

Fig. 150



Li. 50
154

15E




Fig. 16A




Fig. 16B




Fig. 16D






Fig. 16C



16E
L^{*} 60^{*}



16.50




Fig. 17A




Fig. 17B




Fig. 17D

Fig. 17C




Fig. 17F

Fig. 17E





Fig. 18A

18B
Fi 00*





Fig. 18D

Fig. 18C



181.




Fig. 18*




Fig. 19A




Fig. 19B






Fig. 19D



1961



1961




Fig. 19E




Fig. 20A




Fig. 20B




Fig. 20D




Fig. 20C




Fig. 20E

Fig. 20F

1

MULTI-GATE DEVICE INCLUDING SEMICONDUCTOR FIN BETWEEN DIELECTRIC FINS AND METHOD OF FABRICATION THEREOF

BACKGROUND

The semiconductor integrated circuit (IC) industry has experienced exponential growth. Technological advances in IC materials and design have produced generations of ICs where each generation has smaller and more complex circuits than the previous generation. In the course of IC evolution, functional density (i.e., the number of interconnected devices per chip area) has generally increased while geometry size (i.e., the smallest component (or line) that can be created using a fabrication process) has decreased. This scaling down process generally provides benefits by increasing production efficiency and lowering associated costs. Such scaling down has also increased the complexity of processing and manufacturing ICs.

Recently, multi-gate devices have been introduced in an effort to improve gate control by increasing gate-channel coupling, reduce OFF-state current, and reduce short-channel effects (SCEs). One such multi-gate device that has been introduced is the fin field-effect transistor (FinFET). The FinFET gets its name from the fin-like structure which extends from a substrate on which it is formed, and which is used to form the FET channel. Another multi-gate device, introduced in part to address performance challenges associated with FinFETs, is the gate-all-around (GAA) transistor. GAA devices get their name from the gate structure which can extend around the channel region providing access to the channel on four sides. GAA devices are compatible with conventional complementary metal-oxide-semiconductor (CMOS) processes and their structure allows them to be aggressively scaled while maintaining gate control and mitigating SCEs.

To continue to provide the desired scaling and increased density for multi-gate devices (e.g., FinFETs and GAA devices) in advanced technology nodes, dielectric fins have been introduced to improve the uniformity of fins (including semiconductor fins and dielectric fins) and define space for source/drain (S/D) features. Sacrificial cladding layers comprising semiconductor materials may also be introduced to fill between semiconductor fins and dielectric fins to reserve space for metal gate stacks in a replacement gate process. However, the existence of sacrificial cladding layers imposes etching depth limitations during forming S/D recesses, non-uniformity during inner spacer formation, and cleaning complexity during channel layer release. Therefore, while the current methods have been satisfactory in many respects, challenges with respect to performance of the resulting device may not be satisfactory in all respects.

BRIEF DESCRIPTION OF THE DRAWINGS

The present disclosure is best understood from the following detailed description when read with the accompanying figures. It is emphasized that, in accordance with the standard practice in the industry, various features are not drawn to scale and are used for illustration purposes only. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

FIGS. 1A and 1B show a flow chart of a method for forming a multi-gate device, according to one or more aspects of the present disclosure.

2

FIGS. 2A, 3A, 4A, 5A, 6A, 7A, 8A, 9A, 10A, 11A, 12A, 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A illustrate perspective views of a semiconductor structure during a fabrication process according to the method of FIGS. 1A and 1B, according to aspects of the present disclosure.

FIGS. 2B, 3B, 4B, 5B, 6B, 7B, 8B, 9B, 9C, 9D, 10B, 10C, 10D, 10E, 10F, 11B, 11C, 11D, 11E, 11F, 12B, 12C, 12D, 12E, 12F, 13B, 13C, 13D, 13E, 13F, 14B, 14C, 14D, 14E, 14F, 15B, 15C, 15D, 15E, 15F, 16B, 16C, 16D, 16E, 16F, 17B, 17C, 17D, 17E, 17F, 18B, 18C, 18D, 18E, 18F, 19B, 19C, 19D, 19E, 19F, 20B, 20C, 20D, 20E, and 20F illustrate cross-sectional views of a semiconductor structure during a fabrication process according to the method of FIGS. 1A and 1B, according to aspects of the present disclosure.

DETAILED DESCRIPTION

The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. Still further, when a number or a range of numbers is described with “about,” “approximate,” and the like, the term is intended to encompass numbers that are within $\pm 10\%$ of the number described, unless otherwise specified. For example, the term “about 5 nm” encompasses the dimension range from 4.5 nm to 5.5 nm.

The present disclosure is generally related to semiconductor devices and fabrication methods, and more particularly to fabricating multi-gate devices with dielectric fins and sacrificial cladding layers in advanced technology nodes. It is noted that multi-gate devices include those transistors whose gate structures are formed on at least two-sides of a channel region. These multi-gate devices may include a p-type metal-oxide-semiconductor device or an n-type metal-oxide-semiconductor device. Specific examples may be presented and referred to herein as FinFET, on account of their fin-like structure. Also presented herein are embodiments of a type of multi-gate transistor referred to as a gate-all-around (GAA) device. A GAA device includes any device that has its gate structure, or portion thereof, formed on 4-sides of a channel region (e.g., surrounding a portion of a channel region). Devices presented herein also include embodiments that have channel

regions disposed in nanosheet channel(s), nanowire channel (s), bar-shaped channel(s), and/or other suitable channel configurations. Presented herein are embodiments of devices that may have one or more channel regions (e.g., nanowires/nanosheets) associated with a single, contiguous gate structure. However, one of ordinary skill would recognize that the teaching can apply to a single channel (e.g., single nanowire/nanosheet) or any number of channels. One of ordinary skill may recognize other examples of semiconductor devices that may benefit from aspects of the present disclosure.

Embodiments of the present disclosure offer advantages over the existing art, though it is understood that other embodiments may offer different advantages, not all advantages are necessarily discussed herein, and no particular advantage is required for all embodiments. For example, embodiments discussed herein include methods and structures for providing dielectric fins for improving fin uniformity and defining space for source/drain (S/D) features, and a sacrificial cladding layer with amorphous or polycrystalline semiconductor material for reserving space for metal gate stacks. Embodiments discussed herein also includes removing the sacrificial cladding layer prior to the dummy gate structure formation. By removing the sacrificial cladding layers, S/D recesses may be formed above the isolation features to avoid forming a deep trench below the bottom-most channel layer, which in turn reduces leakage current through the semiconductor substrate. Further, by removing the sacrificial cladding layer, it becomes easier to maintain inner spacer length uniformity, as there is no need to balance etching rates in lateral etching sacrificial epitaxial layers and sacrificial cladding layer for forming inner spacer cavities. Still further, by removing the sacrificial cladding layer, it becomes easier to clean the gate trench during the release of channel layers. Otherwise the different material compositions between sacrificial epitaxial layers and the sacrificial cladding layer increase the difficulty of channel layer release with one etchant and increase the risk of over etching the channel layers.

Illustrated in FIGS. 1A and 1B is a method **100** of semiconductor fabrication including fabrication of multi-gate devices. The method **100** is merely an example, and is not intended to limit the present disclosure beyond what is explicitly recited in the claims. Additional operations can be provided before, during, and after the method **100**, and some operations described can be replaced, eliminated, or moved around for additional embodiments of the method. The method **100** is described below in conjunction with FIGS. 2A-20F. FIGS. 2A, 3A, 4A, 5A, 6A, 7A, 8A, 9A, 10A, 11A, 12A, 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A represent perspective views of an embodiment of a semiconductor device **200** according to various stages of the method **100** of FIGS. 1A and 1B. FIGS. 2B, 3B, 4B, 5B, 6B, 7B, and 8B are cross-sectional views taken in the X-Z plane along the B-B line in the corresponding figures numbered with suffix "A", which cut through a gate region and perpendicular to a lengthwise direction of a channel region of the to-be-formed multi-gate device. FIGS. 9B, 10B, 11B, 12B, 13B, 14B, 15B, 16B, 17B, 18B, 19B, and 20B are cross-sectional views taken in the X-Y plane along the B-B line in the corresponding figures numbered with suffix "A", which cut through one of the sacrificial epitaxial layers. FIGS. 9C, 10C, 11C, 12C, 13C, 14C, 15C, 16C, 17C, 18C, 19C, and 20C are cross-sectional views taken in the X-Z plane along the C-C line in the corresponding figures numbered with suffix "A", which cut through a gate region and perpendicular to a lengthwise direction of a channel region of the to-be-formed multi-gate device. FIGS. 9D,

10D, 11D, 12D, 13D, 14D, 15D, 16D, 17D, 18D, 19D, and 20D are cross-sectional views taken in the X-Z plane along the D-D line in the corresponding figures numbered with suffix "A", which cut through a gate sidewall spacer region and perpendicular to a lengthwise direction of a channel region of the to-be-formed multi-gate device. FIGS. 10E, 11E, 12E, 13E, 14E, 15E, 16E, 17E, 18E, 19E, and 20E are cross-sectional views taken in the X-Z plane along the E-E line in the corresponding figures numbered with suffix "A", which cut through a source/drain region and perpendicular to a lengthwise direction of a channel region of the to-be-formed multi-gate device. FIGS. 10F, 11F, 12F, 13F, 14F, 15F, 16F, 17F, 18F, 19F, and 20F are cross-sectional views taken in the Y-Z plane along the F-F line in the corresponding figures numbered with suffix "A", which cut through a channel region and adjacent source/drain regions of the to-be-formed multi-gate device.

As with the other method embodiments and exemplary devices discussed herein, it is understood that parts of the semiconductor device **200** may be fabricated by a CMOS technology process flow, and thus some processes are only briefly described herein. Further, the exemplary semiconductor devices may include various other devices and features, such as other types of devices such as additional transistors, bipolar junction transistors, resistors, capacitors, inductors, diodes, fuses, static random access memory (SRAM) and/or other logic circuits, etc., but is simplified for a better understanding of the inventive concepts of the present disclosure. In some embodiments, the exemplary devices include a plurality of semiconductor devices (e.g., transistors), including P-FETs, N-FETs, etc., which may be interconnected. Moreover, it is noted that the process steps of method **100**, including any descriptions given with reference to FIGS. 2A-20F, as with the remainder of the method and exemplary figures provided in this disclosure, are merely exemplary and are not intended to be limiting beyond what is specifically recited in the claims that follow.

The method **100** at operation **102** (FIG. 1A) provides (or is provided with) a semiconductor device (or device) **200**. Referring to FIGS. 2A and 2B, the device **200** includes a substrate **202** and an epitaxial stack **204** above the substrate **202**. In some embodiments, the substrate **202** may be a semiconductor substrate such as a silicon substrate. The substrate **202** may include various layers, including conductive or insulating layers formed on a semiconductor substrate. The substrate **202** may include various doping configurations depending on design requirements as is known in the art. For example, different doping profiles (e.g., n-wells, p-wells) may be formed on the substrate **202** in regions designed for different device types (e.g., n-type field effect transistors (N-FET), p-type field effect transistors (P-FET)). The suitable doping may include ion implantation of dopants and/or diffusion processes. The substrate **202** may have isolation features (e.g., shallow trench isolation (STI) features) interposing the regions providing different device types. The substrate **202** may also include other semiconductors such as germanium, silicon carbide (SiC), silicon germanium (SiGe), or diamond. Alternatively, the substrate **202** may include a compound semiconductor and/or an alloy semiconductor. Further, the substrate **202** may optionally include an epitaxial layer (epi-layer), may be strained for performance enhancement, may include a silicon-on-insulator (SOI) structure, and/or may have other suitable enhancement features.

The epitaxial stack **204** includes epitaxial layers **206** of a first composition interposed by epitaxial layers **208** of a second composition. The first and second compositions can

5

be different. The epitaxial layers **208** may include the same composition as the substrate **202**. In the illustrated embodiment, the epitaxial layers **206** are silicon germanium (SiGe) and the epitaxial layers **208** are silicon (Si). However, other embodiments are possible including those that provide for a first composition and a second composition having different oxidation rates and/or etch selectivity. For example, in some embodiments, either of the epitaxial layers **206**, **208** of the first composition or the second composition may include other materials such as germanium, a compound semiconductor such as silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide, an alloy semiconductor such as SiGe, GaAsP, AlInAs, AlGaAs, InGaAs, GaInP, and/or GaInAsP, or combinations thereof. In some embodiments, the epitaxial layers **206** and **208** are substantially dopant-free (i.e., having an extrinsic dopant concentration from about 0 cm^{-3} to about $1 \times 10^{17}\text{ cm}^{-3}$), where for example, no intentional doping is performed during the epitaxial growth process. By way of example, epitaxial growth of the epitaxial layers **206**, **208** of the first composition or the second composition may be performed by a molecular beam epitaxy (MBE) process, a metalorganic chemical vapor deposition (MOCVD) process, and/or other suitable epitaxial growth processes. In various embodiments, the substrate **202** is a crystalline substrate, and the epitaxial layers **206**, **208** are crystalline semiconductor layers.

In some embodiments, each epitaxial layer **206** has a thickness ranging from about 4 nanometers (nm) to about 8 nm. The epitaxial layers **206** may be substantially uniform in thickness. Yet the top epitaxial layer **206** may be thinner (e.g., half the thickness) than other epitaxial layers **206** thereunder in some embodiments. The top epitaxial layer **206** functions as a capping layer providing protections to other epitaxial layers in subsequent processes. In some embodiments, each epitaxial layer **208** has a thickness ranging from about 4 nm to about 8 nm. In some embodiments, the epitaxial layers **208** of the stack are substantially uniform in thickness. As described in more detail below, the epitaxial layers **208** or portions thereof may form channel member(s) of the subsequently-formed multi-gate device **200** and the thickness is chosen based on device performance considerations. The term channel member(s) (or channel layer(s)) is used herein to designate any material portion for channel(s) in a transistor with nanoscale, or even microscale dimensions, and having an elongate shape, regardless of the cross-sectional shape of this portion. Thus, this term designates both circular and substantially circular cross-section elongate material portions, and beam or bar-shaped material portions including for example a cylindrical in shape or substantially rectangular cross-section. The epitaxial layers **206** in channel regions(s) may eventually be removed and serve to define a vertical distance between adjacent channel members for a subsequently-formed multi-gate device and the thickness is chosen based on device performance considerations. Accordingly, the epitaxial layers **206** may also be referred to as sacrificial layers, and epitaxial layers **208** may also be referred to as channel layers.

It is noted that four (4) layers of the epitaxial layers **206** and three (3) layers of the epitaxial layers **208** are alternately arranged as illustrated in FIGS. 2A and 2B, which is for illustrative purposes only and not intended to be limiting beyond what is specifically recited in the claims. It can be appreciated that any number of epitaxial layers can be formed in the epitaxial stack **204**; the number of layers depending on the desired number of channels members for

6

the device **200**. In some embodiments, the number of epitaxial layers **208** is between 2 and 10. It is also noted that while the epitaxial layers **206**, **208** are shown as having a particular stacking sequence, where an epitaxial layer **206** is the topmost layer of the epitaxial stack **204**, other configurations are possible. For example, in some cases, an epitaxial layer **208** may alternatively be the topmost layer of the epitaxial stack **204**. Stated another way, the order of growth for the epitaxial layers **206**, **208**, and thus their stacking sequence, may be switched or otherwise be different than what is shown in the figures, while remaining within the scope of the present disclosure.

The method **100** then proceeds to operation **104** (FIG. 1A) where semiconductor fins (also referred to as device fins or fin elements) are formed by patterning. With reference to the example of FIGS. 3A and 3B, in an embodiment of operation **104**, a plurality of semiconductor fins **210** extending from the substrate **202** are formed. In various embodiments, each of the semiconductor fins **210** includes a base portion **203** (also referred to as mesa) formed from the substrate **202** and an epitaxial stack portion **204** formed from portions of each of the epitaxial layers of the epitaxial stack including epitaxial layers **206** and **208**. The semiconductor fins **210** may be fabricated using suitable processes including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over a substrate and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers, or mandrels, may then be used to pattern the semiconductor fins **210** by etching initial epitaxial stack **204**. The etching process can include dry etching, wet etching, reactive ion etching (RIE), and/or other suitable processes.

In the illustrated embodiment, a hard mask (HM) layer **212** is formed over the epitaxial stack **204** prior to patterning the semiconductor fins **210**. In some embodiments, the HM layer **212** includes an oxide layer **212A** (e.g., a pad oxide layer that may include silicon oxide) and a nitride layer **212B** (e.g., a pad nitride layer that may include silicon nitride) formed over the oxide layer **212A**. The oxide layer **212A** may act as an adhesion layer between the epitaxial stack **204** and the nitride layer **212B** and may act as an etch stop layer for etching the nitride layer **212B**. In some examples, the HM layer **212** includes thermally grown oxide, chemical vapor deposition (CVD)-deposited oxide, and/or atomic layer deposition (ALD)-deposited oxide. In some embodiments, the HM layer **212** includes a nitride layer deposited by CVD and/or other suitable technique.

The semiconductor fins **210** may subsequently be fabricated using suitable processes including photolithography and etch processes. The photolithography process may include forming a photoresist layer (not shown) over the HM layer **212**, exposing the resist to a pattern, performing post-exposure bake processes, and developing the resist to form a masking element including the resist. In some embodiments, patterning the resist to form the masking element may be performed using an electron beam (e-beam) lithography process. The masking element may then be used to protect regions of the substrate **202**, and layers formed thereupon, while an etch process forms trenches **214** in unprotected regions through the HM layer **212**, through the epitaxial stack **204**, and into the substrate **202**, thereby

leaving the plurality of extending semiconductor fins **210**. The trenches **214** may be etched using dry etching, wet etching, RIE, and/or other suitable processes. In some examples, a width **W1** of the semiconductor fin **210** ranges from about 20 nm to about 30 nm.

Numerous other embodiments of methods to form the semiconductor fins on the substrate may also be used including, for example, defining the fin region (e.g., by mask or isolation regions) and epitaxially growing the epitaxial stack **204** in the form of the semiconductor fins **210**. In some embodiments, forming the semiconductor fins **210** may include a trim process to decrease the width of the semiconductor fins **210**. The trim process may include wet and/or dry etching processes.

At operation **106**, the method **100** (FIG. 1A) forms isolation features, such as shallow trench isolation (STI) features, between the semiconductor fins **210**. Referring to FIGS. 4A and 4B, STI features **220** is disposed on the substrate **202** interposing the semiconductor fins **210**. By way of example, in some embodiments, a dielectric layer is first deposited over the substrate **202**, filling the trenches **214** with dielectric material. In some embodiments, the dielectric layer may include silicon oxide, silicon nitride, silicon oxynitride, fluorine-doped silicate glass (FSG), a low-k dielectric, combinations thereof, and/or other suitable materials. In various examples, the dielectric layer may be deposited by a CVD process, a SACVD process, a flowable CVD process, an ALD process, a PVD process, and/or other suitable process. In some embodiments, after deposition of the dielectric layer, the device **200** may be annealed, for example, to improve the quality of the dielectric layer. In some embodiments, the dielectric layer may include a multi-layer structure, for example, having one or more liner layers.

In some embodiments of forming the isolation (STI) features, after deposition of the dielectric layer, the deposited dielectric material is thinned and planarized, for example by a chemical mechanical polishing (CMP) process. In some embodiments, the HM layer **212** functions as a CMP stop layer. Subsequently, the dielectric layer interposing the semiconductor fins **210** are recessed. Still referring to the example of FIGS. 4A and 4B, the STI features **220** are recessed providing the semiconductor fins **210** extending above the STI features **220**. In some embodiments, the recessing process may include a dry etching process, a wet etching process, and/or a combination thereof. In some embodiments, a recessing depth is controlled (e.g., by controlling an etching time) so as to result in a desired height of the exposed upper portion of the semiconductor fins **210**. In the illustrated embodiment, the desired height exposes each of the layers of the epitaxial stack **204**. In furtherance of the embodiment, a top surface of the STI features **220** is recessed below the bottommost epitaxial layer **206**.

At operation **108**, the method **100** (FIG. 1A) deposits a cladding layer on top and sidewall surfaces of the semiconductor fins. Referring to FIGS. 5A and 5B, in the illustrated embodiment, the cladding layer **222** is selectively deposited over the device **200**. In particular, the cladding layer **222** may be selectively and conformally deposited over the exposed surfaces of the semiconductor fins **210**. In various embodiments, the cladding layer **222** is not deposited on top surfaces of the STI features **220** between the semiconductor fins **210**. For example, the cladding layer **222** may be a semiconductor layer and deposited by an epitaxial growing process, such that the epitaxial growth of the cladding layer **222** is limited to exposed semiconductor surfaces of the semiconductor fins **210**, which functions as a seed layer, but

not on dielectric material surfaces of the STI features **220**. Alternatively, the cladding layer **222** may be deposited as a blanket layer covering the device **200**. Subsequently, horizontal portions of the cladding layer **222** are removed in an anisotropic etch process, such as a dry etching process (e.g., RIE etching), leaving remaining portions on top and sidewall surfaces of the semiconductor fins **210**. By way of example, the cladding layer **222** may be deposited by an MBE process, an MOCVD process, an ALD process, and/or other suitable deposition processes. As will be explained in detail below, the cladding layer **222** reserves a space for subsequently formed metal gate stack and will be removed in a subsequent processing stage. Therefore, the cladding layer **222** is also referred to as a sacrificial cladding layer.

In some embodiments, the cladding layer **222** includes the same semiconductor material as the epitaxial layers **206**, such as silicon germanium (SiGe), but in difference germanium concentrations. For example, the molar ratio of germanium may range from about 15% to about 25% in the epitaxial layers **206**, and the molar ratio of germanium may range from about 40% to about 50% in the cladding layer **222**. The difference in germanium concentration provides etch selectivity between the cladding layer **222** and the epitaxial layers **206**. In some alternative embodiments, the cladding layer **222** includes the same semiconductor material as the epitaxial layers **206**, such as silicon germanium (SiGe), including the same germanium concentration. In furtherance of the embodiment, an oxide liner (not shown) may be formed on exposed semiconductor surfaces of the semiconductor fins **210** prior to the deposition of the cladding layer **222**. The oxide liner separates the cladding layer **222** from the epitaxial layers **206** and protects the epitaxial layers **206** in subsequent removal of the cladding layer **222**. The oxide liner is formed by oxidizing exposed semiconductor surfaces of the semiconductor fins **210**. The oxidation process results in the oxide liner having a determined thickness. For example, the oxide liner may have a thickness from about 1 nm to about 3 nm. In some embodiments, the oxidation process comprises a rapid thermal oxidation (RTO) process, high pressure oxidation (HPO), chemical oxidation process, in-situ stream generation (ISSG) process, or enhanced in-situ stream generation (EISSG) process. In some embodiments, the RTO process is performed at a temperature of about 400° C. to about 700° C., using O₂ and O₃ as reaction gases, for about 1 second to about 30 seconds. In other embodiments, an HPO is performed using a process gas of O₂, O₂+N₂, N₂, or the like, at a pressure from about 1 atm to about 25 atm and a temperature from about 300° C. to about 700° C., for about 1 minute to about 10 minutes. Examples of a chemical oxidation process include wet SPM clean, wet O₃/H₂O, or the like. The O₃ may have a concentration of about 1 ppm to about 50 ppm.

In some embodiments, the semiconductor material in the cladding layer **222** is in either amorphous form or polycrystalline form, such as amorphous SiGe or polycrystalline SiGe in some embodiments. In yet some embodiments, the cladding layer **222** may have a mixture of semiconductor material in both amorphous form and polycrystalline form, such as 60% SiGe in amorphous form and 40% SiGe in polycrystalline form. The term “amorphous or polycrystalline” is used herein to designate composition in amorphous form, polycrystalline form, or a combination thereof.

At operation **110**, the method **100** (FIG. 1A) forms dielectric fins between adjacent semiconductor fins. Referring to FIGS. 6A and 6B, in an embodiment of operation **110**, a dielectric layer **224** is deposited conformally within the trenches **214** including along sidewalls of the cladding

layer **222** and along a top surface of the STI features **220**. Thereafter, a dielectric layer **226** is deposited over the dielectric layer **224**. In at least some embodiments, the dielectric layers **224**, **226** may collectively define a dielectric fin **228** (or hybrid fin **228**). In some cases, a dielectric fin **228** may further include a high-k dielectric layer formed over the dielectric layers **224** and **226**, for example after recessing of the dielectric layers **224** and **226**, as discussed below. Generally, and in some embodiments, the dielectric layers **224** and **226** may include SiN, SiCN, SiOC, SiOCN, SiOx, or other appropriate material. In some examples, the dielectric layer **224** may include a low-k dielectric layer, and the dielectric layer **226** may include a flowable oxide layer. In various cases, the dielectric layers **224** and **226** may be deposited by a CVD process, an ALD process, a PVD process, a spin-coating and baking process, and/or other suitable process. In some examples, after depositing the dielectric layers **224** and **226**, a CMP process may be performed to remove excess material portions and to planarize a top surface of the device **200**.

The method **100** at operation **110** may further include a recessing process, a high-k dielectric layer deposition process, and a CMP process. Still referring to FIGS. **6A** and **6B**, in an embodiment of operation **110**, a recessing process is performed to remove top portions of the dielectric layers **224** and **226**. In some embodiments, the recessing process may include a dry etching process, a wet etching process, and/or a combination thereof. In some embodiments, a recessing depth is controlled (e.g., by controlling an etching time) to result in a desired recess depth. In some embodiments, the recessing process may optionally remove at least part of the cladding layer **222**. After performing the recessing process, and in a further embodiment of operation **110**, a high-k dielectric layer **230** is deposited within trenches formed by the recessing process. In some embodiments, the high-k dielectric layer **230** may include HfO₂, ZrO₂, HfAlOx, HfSiOx, Y₂O₃, Al₂O₃, or another high-k material. The high-k dielectric layer **230** may be deposited by a CVD process, an ALD process, a PVD process, and/or other suitable process. After deposition of the high-k dielectric layer **230**, and in a further embodiment of operation **110**, a CMP process is performed to remove excess material portions and to planarize a top surface of the device **200**. In some examples, the CMP process removes a portion of the cladding layer **222** from the top of the semiconductor fins **210** to expose the HM layer **212**. Thus, in various cases, a dielectric fin **228** is defined as having a lower portion including the recessed portions of the dielectric layers **224**, **226** and an upper portion including the high-k dielectric layer **230**. In some examples, a height of the high-k dielectric layer **230** may be about 20 nm to about 30 nm with a width W₂ ranging from about 15 nm to about 25 nm, and a pitch P of the dielectric fins **228** may range from about 60 nm to about 70 nm. In some cases, a dielectric fin **228** may be alternatively described as a bi-layer dielectric having a high-k upper portion and a low-k lower portion. In some examples, a height ratio of the upper portion to the lower portion may be about 1:20 to about 20:1. The height ratio may be adjusted, for example, by changing the recess depth and thus the height of the high-K dielectric layer **230**, as noted above. In the illustrated embodiment, the recessed top surface of the dielectric layers **224** and **226** is substantially level (or termed as coplanar) with a top surface of the top epitaxial layer **208**. In some embodiments, the dielectric fins **228** are used to effectively prevent the undesirable lateral

merging of the epitaxial S/D features formed on adjacent semiconductor fins **210**, as will be discussed in more detail below.

At operation **112**, the method **100** (FIG. **1A**) removes the HM layer **212** and a top portion of the cladding layer **222**. Referring to FIGS. **7A** and **7B**, in an embodiment of operation **112**, the HM layer **212** and a top portion of the cladding layer **222** may initially be etched-back. The topmost epitaxial layer **206** may act as an etch stop layer for etching the HM layer **212** and be subsequently removed. The top portion of the cladding layer **222** may be removed together with the topmost epitaxial layer **206** by the same etchant that targets the same semiconductor material, such as SiGe. In some embodiments, a top surface of the etched-back cladding layer **222** is substantially level with top surfaces of the topmost epitaxial layer **208** of the semiconductor fins **210**. In some embodiments, the etch-back of the HM layer **212** and the top portion of the cladding layer **222** may be performed using a wet etch process, a dry etch process, a multiple-step etch process, and/or a combination thereof. The HM layer **212** may be removed, for example, by a wet etching process using H₃PO₄ or other suitable etchants.

At operation **114**, the method **100** (FIG. **1A**) removes the remaining portion of the cladding layer **222**. Referring to FIGS. **8A** and **8B**, in an embodiment of operation **114**, the epitaxial layers **206** and the cladding layer **222** both include SiGe but with different germanium concentrations, allowing for the selective removal of the cladding layer **222**. In an embodiment, the cladding layer **222** is removed by a selective wet etching process. In some embodiments, the selective wet etching includes an APM etch (e.g., ammonia hydroxide-hydrogen peroxide-water mixture). In some embodiments, the selective removal includes SiGe oxidation followed by a SiGeOx removal. For example, the oxidation may be provided by O₃ clean and then SiGeOx removed by an etchant such as NH₄OH. In an alternative embodiment of operation **114**, the epitaxial layers **206** and the cladding layer **222** both include SiGe with the same germanium concentration but separated by an oxide liner formed on the semiconductor fins. The oxide liner functions as an etch stop layer during the removal of the cladding layer **222** and protects the epitaxial layers **206** underneath from etch loss. The cladding layer **222** may be removed in an etching process that includes dry etching, wet etching, reactive ion etching (RIE), and/or other suitable processes. After the removal of the cladding layer **222**, trenches **232** are formed between opposing sidewalls of the semiconductor fins **210** and the dielectric fins **228**. A top surface of the STI features **220** is exposed in the trenches **232**. A distance H from the top surface of the top epitaxial layer **208** to the top surface of the STI features **220** may range from about 60 nm to about 70 nm.

The method **100** then proceeds to operation **116** (FIG. **1A**) where a dummy gate structure is formed. While the present discussion is directed to a replacement gate (or gate-last) process whereby a dummy gate structure is formed and subsequently replaced, other configurations may be possible. With reference to FIGS. **9A-9D**, a dummy gate structure **234** is formed. The dummy gate structure **234** will be replaced by a final gate stack at a subsequent processing stage of the device **200**. In particular, the dummy gate structure **234** may be replaced at a later processing stage by a high-k dielectric layer (HK) and metal gate electrode (MG), as will be discussed in more detail below. In some embodiments, the dummy gate structure **234** is disposed over the semiconductor fins **210**, the dielectric fins **228**, and the STI features **220**. The portion of the semiconductor fins

210 underlying the dummy gate structure **234** may be referred to as the channel region. The dummy gate structure **234** may also define source/drain (S/D) regions of the semiconductor fins **210**, for example, the regions of the semiconductor fin **210** adjacent and on opposing sides of the channel region.

In some embodiments, the dummy gate structure **234** is formed by various process steps such as layer deposition, patterning, etching, as well as other suitable processing steps. Exemplary layer deposition processes include CVD (including low-pressure CVD, plasma-enhanced CVD, and/or flowable CVD), PVD, ALD, thermal oxidation, e-beam evaporation, or other suitable deposition techniques, or combinations thereof. In some embodiments, the dummy gate structure **234** includes a dummy dielectric layer and a dummy electrode layer. In some embodiments, the dummy dielectric layer may include SiO₂, silicon nitride, a high-k dielectric material and/or other suitable material. Subsequently, the dummy electrode layer is deposited. In some embodiments, the dummy electrode layer may include polycrystalline silicon (polysilicon). In forming the dummy gate structure for example, the patterning process includes a lithography process (e.g., photolithography or e-beam lithography) which may further include photoresist coating (e.g., spin-on coating), soft baking, mask aligning, exposure, post-exposure baking, photoresist developing, rinsing, drying (e.g., spin-drying and/or hard baking), other suitable lithography techniques, and/or combinations thereof. In some embodiments, the etching process may include dry etching (e.g., RIE etching), wet etching, and/or other etching methods. In some embodiments, the dummy gate structure **234** is patterned through a hard mask **236**. The hard mask **236** may include multiple layers, such as an oxide layer and a nitride layer over the oxide layer. In some embodiments, after formation of the dummy gate structure **234**, the dummy dielectric layer is removed from the S/D regions of the semiconductor fins **210**. The etch process may include a wet etch, a dry etch, and/or a combination thereof. The etch process is chosen to selectively etch the dummy dielectric layer without substantially etching the semiconductor fins **210**, the hard mask **236**, and the dummy electrode layer.

Referring to FIGS. 9B and 9C, due to the removal of the cladding layer **222** prior to the forming of the dummy gate structure **234**, the dummy gate structure **234** is also formed in the trenches **232**. That is, a bottom portion of the dummy gate structure **234** is laterally stacked between the semiconductor fins **210** and the dielectric fins **228**. The bottom portion of the dummy gate structure **234** is in contact with the top surface of the STI features **220**. In the illustrated embodiment, as the base portion **203** of the semiconductor fins **210** protrudes above the top surface of the STI features **220**, a bottommost portion of the dummy gate structure **234** is below a bottom surface of the bottom epitaxial layer **206**.

At operation **118**, the method **100** (FIG. 1A) forms gate sidewall spacers on sidewall surfaces of the dummy gate structure **234**. With reference to FIGS. 10A-10F, gate sidewall spacers **242** are formed. The gate sidewall spacers **242** may have a thickness from about 2 nm to about 10 nm. In some examples, the gate sidewall spacers **242** may include a dielectric material such as silicon oxide, silicon nitride, silicon carbide, silicon oxynitride, SiCN, silicon oxycarbide, SiOCN, a low-k material, and/or combinations thereof. In some embodiments, the gate sidewall spacers **242** include multiple layers, such as a liner spacer layer and a main spacer layer, and the like. By way of example, the gate sidewall spacers **242** may be formed by conformally depositing a dielectric material over the device **200** using pro-

cesses such as a CVD process, a subatmospheric CVD (SACVD) process, a flowable CVD process, an ALD process, a PVD process, or other suitable process. Following the conformal deposition of the dielectric material, portions of the dielectric material used to form the gate sidewall spacers **242** may be etched-back to expose portions of the semiconductor fins **210** not covered by the dummy gate structures **234** (e.g., for example, in source/drain regions). In some cases, the etch-back process removes portions of dielectric material used to form the gate sidewall spacers **242** along a top surface of the dummy gate structure **234**, thereby exposing the hard mask layer **236**. In some embodiments, the etch-back process may include a wet etch process, a dry etch process, a multiple-step etch process, and/or a combination thereof. It is noted that after the etch-back process, the gate sidewall spacers **242** remain disposed on sidewall surfaces of the dummy gate structure **234**. A distance DO between two external sidewalls of the gate sidewall spacers **242** may range from about 20 nm to about 30 nm (FIG. 10F).

Referring to FIGS. 10B and 10D, due to the removal of the cladding layer **222** prior to the forming of the dummy gate structure **234**, the gate sidewall spacers **242** are also formed in the trenches **232**. That is, a bottom portion of the gate sidewall spacers **242** is laterally stacked between the semiconductor fins **210** and the dielectric fins **228**. The bottom portion of the gate sidewall spacers **242** is in contact with the top surface of the STI features **220**. In the illustrated embodiment, as the base portion **203** of the semiconductor fins **210** protrudes above the top surface of the STI features **220**, a bottommost portion of the gate sidewall spacers **242** is below a bottom surface of the bottom epitaxial layer **206**.

At operation **120**, the method **100** (FIG. 1B) recesses the semiconductor fins **210** in the S/D regions in forming S/D recesses. With reference to FIGS. 11A-11F, by recessing the semiconductor fins **210** that separate trenches **232** in the S/D regions, adjacent trenches **232** are adjoined, in forming larger trenches between adjacent dielectric fins **228** denoted as S/D recesses **246**. In some embodiments of operation **120**, the S/D recesses **246** is formed by an S/D etch process. An S/D etch process is performed to remove portions of the semiconductor fins **210** not covered by the dummy gate structure **234** and the gate sidewall spacers **242** (e.g., in S/D regions) and that were previously exposed (e.g., during the gate sidewall spacers etch-back process). In particular, the S/D etch process may serve to remove portions of the epitaxial layers **206** and **208** in the S/D regions of the device **200** to expose underlying base portions **203** of the semiconductor fins **210**. In some embodiments, the S/D etch process may include a dry etching process, a wet etching process, and/or a combination thereof.

In some embodiments, a recessing depth is controlled (e.g., by controlling an etching time) such that the base portion **203** remains protruding above the STI features **220**. Referring to FIG. 11E, in the illustrated embodiment, the S/D etch process stops when the bottom epitaxial layer **206** (represented by dotted box **206'**) is removed. The top surface S203 of the base portion **203** may have a dishing profile due to certain etch loss during the S/D etch process. The tips of the dishing profile may align with a bottom surface of the bottom epitaxial layer **206** in the channel region. The top surface S203 is above the STI features **220**. If the cladding layer **222** is not removed, the base portion **203** may have to be recessed below the STI features **220** to fully expose the cladding layer **222** in order to avoid shorting between subsequently formed S/D features and metal gate stacks. A top surface of the base portion **203** in such a scenario is represented by dotted line S203', which is below the STI

13

features **220**. With the elevated top surface **S203** instead of **S203'**, the S/D trenches **246** becomes shallower (a distance **D1** measured from bottom of the S/D recess **246** to the bottom surface of the epitaxial stack **204** may be less than about 5 nm), which translates to a thicker base portion **203** and less gate drive applied on the semiconductor substrate underneath the subsequently formed S/D features. In some examples, the base portion **203** may gain extra thickness from about 5 nm to about 15 nm. The substrate leakage is thus suppressed.

At operation **122**, the method **100** (FIG. 1B) forms inner spacer cavities. With reference to FIGS. 12A-12F, by laterally recessing the epitaxial layers **206** through S/D recesses **246**, inner spacer cavities **248** are formed. In some embodiments of operation **122**, a lateral etching (or horizontal recessing) is performed to recess the epitaxial layers **206** to form inner spacer cavities **248**. The amount of etching of the epitaxial layers **206** is in a range from about 2 nm to about 10 nm in some embodiments. In furtherance of some embodiments, end portions (edges) of the recessed epitaxial layers **206** are substantially flush with the sidewall surfaces of the dummy gate structure **234**. Here, "being substantially flush" means the difference in the relative position is less than about 1 nm. When the epitaxial layers **206** are SiGe, the lateral etching process may use an etchant selected from, but not limited to, ammonium hydroxide (NH₄OH), tetramethylammonium hydroxide (TMAH), ethylenediamine pyrocatechol (EDP), and potassium hydroxide (KOH) solutions.

Referring to FIGS. 12B and 12D, as the cladding layer **222** has been removed and replaced by the dummy gate structure **234** and the gate sidewall spacers **242**, the etchant selected for lateral etching only needs to selectively etch the epitaxial layer **206**, not the cladding layer **222**, which simplifies the etching process. If the cladding layer **222** still presents in locations where the dummy gate structure **234** and the gate sidewall spacers **242** presently are, etching rates would be different for the epitaxial layer **206** and the cladding layer **222** due to different material compositions (e.g., different germanium concentrations), which would result in poor uniformity of inner spacer cavity dimensions.

At operation **124**, the method **100** (FIG. 1B) forms inner spacers. With reference to FIGS. 13A-13F, inner spacers **250** are formed in the inner spacer cavities **248**. A length **D2** of the inner spacers **250** (along the Y-direction) may range from about 3 nm to about 8 nm, in some embodiments. In some embodiments of operation **124**, an insulating layer is formed on the lateral ends of the epitaxial layers **206** to fill the inner spacer cavities **248**, thereby forming inner spacers **250**. The insulating layer may include a dielectric material, such as SiN, SiOC, SiOCN, SiCN, SiO₂, and/or other suitable material. In some embodiments, the insulating layer is conformally deposited, for example, by ALD or any other suitable method. After the conformal deposition of the insulating layer, an etch-back process is performed to partially remove the insulating layer from outside of the inner spacer cavities **248**. By this etching the insulating layer remains substantially within the inner spacer cavities **248**. In some examples, the etch-back process may also etch a portion of the high-k dielectric layer **230** of the dielectric fins **228** not covered by the dummy gate structure **234**.

At operation **126**, the method **100** (FIG. 1B) forms S/D features (also referred to as epitaxial S/D features). With reference to FIGS. 14A-14F, S/D features **252** are formed in the S/D recesses **246**. In some embodiments of operation **126**, the S/D features **252** are formed in S/D regions adjacent to and on either side of the dummy gate structure **234**. For example, the S/D features **252** may be formed over the

14

exposed base portions **203** of the semiconductor fins **210** and in contact with the adjacent inner spacers **250** and the channel layers (epitaxial layers **208**). The S/D features **252** is also in contact with sidewalls of the dielectric fins **228** in the X-direction. The dielectric fins **228**, which may have a partially etched-back high-K dielectric layer **230**, effectively prevents the lateral merging of the S/D features **252** formed on adjacent semiconductor fins **210**. Referring to FIG. 14E, in the illustrated embodiment, due to the elevated top surface **S203** of the protruding base portion **203**, the S/D features **252** is not in contact with the top surface of the STI features **220**, even though a bottom portion of the S/D features **252** extends downwardly towards the STI features **220** and is lower than the top surface **S203**. Voids **254** (or gaps) are trapped between the bottom surface of the S/D features **252** and the top surface of the STI features **220**. The voids **254** may be filled with ambient environment conditions (e.g., air, nitrogen).

In some embodiments, the S/D features **252** are formed by epitaxially growing a semiconductor material layer in the S/D regions. In various embodiments, the S/D features **252** may include Ge, Si, GaAs, AlGaAs, SiGe, GaAsP, SiP, or other suitable material. The S/D features **252** may be in-situ doped during the epitaxial process by introducing doping species including: p-type dopants, such as boron or BF₂; n-type dopants, such as phosphorus or arsenic; and/or other suitable dopants including combinations thereof. If the S/D features **252** are not in-situ doped, an implantation process (i.e., a junction implant process) is performed to dope the S/D features **252**. In an exemplary embodiment, the S/D features **252** in an NMOS device include SiP, while those in a PMOS device include GeSnB and/or SiGeSnB. Furthermore, silicidation or germano-silicidation may be formed on the S/D features **252**. For example, silicidation, such as nickel silicide, may be formed by depositing a metal layer over the epitaxial S/D features **252**, annealing the metal layer such that the metal layer reacts with silicon in the S/D features **252** to form the metal silicidation, and thereafter removing the non-reacted metal layer.

At operation **128**, the method **100** (FIG. 1B) forms a contact etch stop layer (CESL) and an inter-layer dielectric (ILD) layer. With reference to FIGS. 15A-15F, a CESL **256** is deposited over the S/D features **252** and an ILD layer **258** is deposited over the CESL **256**. In some embodiments of operation **128**, the CESL **256** includes a silicon nitride layer, silicon oxide layer, a silicon oxynitride layer, and/or other materials known in the art. The CESL **256** may be formed by plasma-enhanced chemical vapor deposition (PECVD) process and/or other suitable deposition or oxidation processes. In some embodiments, the ILD layer **258** includes materials such as tetraethylorthosilicate (TEOS) oxide, undoped silicate glass, or doped silicon oxide such as borophosphosilicate glass (BPSG), fused silica glass (FSG), phosphosilicate glass (PSG), boron doped silicon glass (BSG), and/or other suitable dielectric materials. The ILD layer **258** may be deposited by a PECVD process or other suitable deposition technique. In some embodiments, after formation of the ILD layer **258**, the semiconductor device **200** may be subject to a high thermal budget process to anneal the ILD layer.

In some examples, after depositing the ILD layer, a planarization process may be performed to remove excessive dielectric materials. For example, a planarization process includes a chemical mechanical planarization (CMP) process which removes portions of the ILD layer **258** (and CESL **256**, if present) overlying the dummy gate structure **234** and planarizes a top surface of the semiconductor device

200. In some embodiments, the CMP process also removes the hard mask 236 and exposes the dummy electrode layer of the dummy gate structure 234.

At operation 130, the method 100 (FIG. 1B) recesses the dummy gate structure 234 to form a gate trench 260. With reference to FIGS. 16A-16F, the dummy gate structure 234 is recessed to expose top surfaces of the dielectric fins 228 in the gate trench 260. In some embodiments of operation 130, a recessing depth of the dummy gate structure 234 is controlled (e.g., by controlling an etching time) so as to result in a desired height of the exposed upper portion of the dielectric fins 228. Referring to FIG. 16C, in the illustrated embodiment, the top surface of the recessed dummy gate structure 234 is below top surfaces of the high-k dielectric layer 230 but higher than bottom surfaces of the high-k dielectric layer 230. In other words, sidewalls of the high-k dielectric layer 230 of the dielectric fins 228 are partially exposed in the gate trench 260. Operation 130 may include one or more etching processes that are selective to the material in the dummy gate structure 234. For example, recessing the dummy gate structure 234 may be performed using a selective etch process such as a selective wet etch, a selective dry etch, or a combination thereof.

At operation 132, the method 100 (FIG. 1B) selectively removes the high-k dielectric layer 230 from a dielectric fin 228 at the location where a joint metal gate stack is subsequently formed. With reference to FIGS. 17A-17F, a mask layer 262 is formed over the recessed dummy gate structure 234 with an opening in the mask layer 262 that exposes one of the dielectric fins 228. In some embodiments of operation 132, the mask layer 262 is made of silicon oxide, silicon nitride, silicon carbon nitride, or other suitable material, and patterned using any suitable methods such as a photolithography process, which may include forming a resist layer on the mask layer 262, exposing the resist by a lithography exposure process, performing a post-exposure bake process, developing the photoresist layer to form the patterned photoresist layer that exposes part of the mask layer 262, patterning the mask layer 262, and finally removing the patterned resist layer. In some embodiments, the removal of the high-k dielectric layer 230 may be performed using a selective etch process such as a selective wet etch, a selective dry etch, or a combination thereof. The dielectric layers 224 and 226 of the dielectric fins 228 are exposed in the gate trench 260. The mask layer 262 is subsequently removed.

At operation 134, the method 100 (FIG. 1B) removes the dummy gate structure 234 to extend the gate trench 260 downwardly and expose the STI features 220 in the channel region. With reference to FIGS. 18A-18F, after the removal of the dummy gate structure 234, the epitaxial layers 206 and 208 are exposed in the gate trench 260. In some embodiments, operation 134 may include one or more etching processes that are selective to the material in the dummy gate structure 234. For example, the removal of the dummy gate structure 234 may be performed using a selective etch process such as a selective wet etch, a selective dry etch, or a combination thereof. A final gate structure (e.g., a high-k metal gate stack) may be subsequently formed in the gate trench 260, as will be described below.

At operation 136, the method 100 (FIG. 1B) removes the epitaxial layers 206 from the semiconductor fins 210. With reference to FIGS. 19A-19F, after the removal of the epitaxial layers 206, the epitaxial layers 208 are released in the gate trench 260 as channel members. In some embodiments, the epitaxial layers 206 include SiGe and the epitaxial layers 208 are silicon, allowing for the selective removal of the epitaxial layers 206. In furtherance of some embodiments,

the epitaxial layers 206 are removed by a selective wet etching process. In some embodiments, the selective wet etching includes an APM etch (e.g., ammonia hydroxide-hydrogen peroxide-water mixture). In some embodiments, the selective removal includes SiGe oxidation followed by a SiGeOx removal. For example, the oxidation may be provided by O₃ clean and then SiGeOx removed by an etchant such as NH₄OH.

Due to the removal of the cladding layer 222 prior to the forming of the dummy gate structure 234, operation 136 only needs to selectively etch the epitaxial layers 206 instead of a combination of the epitaxial layer 206 and the cladding layer 222. If the cladding layer 222 is not removed until operation 136, different etch rates between the epitaxial layer 206 and the cladding layer 222 (e.g., as due to different germanium concentrations) may complicate the etching process. For example, the etching time may be extended to ensure both the epitaxial layer 206 and the cladding layer 222 are sufficiently removed, which may in turn damage the channel members 208 in an extended etching process.

The method 100 then proceeds to operation 138 (FIG. 1B) where a gate structure is formed. The gate structure may be the gate of one or more multi-gate transistors. The gate structure may be a high-k metal gate (HK MG) stack, however other compositions are possible. In some embodiments, the gate structure forms the gate associated with the multi-channels provided by the plurality of channel members (e.g., nanosheets or nanowires having gaps therebetween) in the channel region. The resultant structure is shown in FIGS. 20A-20F. In an embodiment of operation 138, a HK MG stack 270 is formed within the gate trench 260 of the device 200 provided by the release of the epitaxial layers 208, described above with reference to prior operation 136. In various embodiments, the HK MG stack 270 includes an interfacial layer (not shown), a high-K gate dielectric layer 272 formed over the interfacial layer, and a gate electrode layer 274 formed over the high-k gate dielectric layer 272. High-k gate dielectrics, as used and described herein, include dielectric materials having a high dielectric constant, for example, greater than that of thermal silicon oxide (~3.9). The gate electrode layer used within HK MG stack may include a metal, metal alloy, or metal silicide. Additionally, the formation of the HK MG stack may include depositions to form various gate materials, one or more liner layers, and one or more CMP processes to remove excessive gate materials and thereby planarize a top surface of the semiconductor device 200. Interposing the HK MG stack 270 and the S/D features 252 is the inner spacers 250, providing isolation.

The HK MG stack 270 includes portions that interpose each of the epitaxial layers (channel members) 208, which form channels of the multi-gate device 200. In some embodiments, the interfacial layer of the HK MG stack 270 may include a dielectric material such as silicon oxide (SiO₂), HfSiO, or silicon oxynitride (SiON). The interfacial layer may be formed by chemical oxidation, thermal oxidation, atomic layer deposition (ALD), chemical vapor deposition (CVD), and/or other suitable method. The high-k gate dielectric layer 272 of the HK MG stack 270 may include a high-K dielectric such as hafnium oxide (HfO₂). Alternatively, the high-k gate dielectric layer 272 of the HK MG stack 270 may include other high-K dielectrics, such as TiO₂, HfZrO, Ta₂O₃, HfSiO₄, ZrO₂, ZrSiO₂, LaO, AlO, ZrO, TiO, Ta₂O₅, Y₂O₃, SrTiO₃ (STO), BaTiO₃ (BTO), BaZrO, HfZrO, HfLaO, HfSiO, LaSiO, AlSiO, HfTaO, HfTiO, (Ba,Sr)TiO₃ (BST), Al₂O₃, Si₃N₄, oxynitrides (SiON), combinations thereof, or other suitable material.

The high-k gate dielectric layer **272** may be formed by ALD, physical vapor deposition (PVD), CVD, oxidation, and/or other suitable methods. As illustrated in FIGS. **20B** and **20C**, in some embodiments, the high-k gate dielectric layer **272** is deposited conformally on sidewalls of the inner spacers **250** and top surfaces of the STI features **220**.

The gate electrode layer **274** of the HK MG stack **270** may include a single layer or alternatively a multi-layer structure, such as various combinations of a metal layer with a selected work function to enhance the device performance (work function metal layer), a liner layer, a wetting layer, an adhesion layer, a metal alloy or a metal silicide. By way of example, the gate electrode layer **274** of HK MG stack **270** may include Ti, Ag, Al, TiAlN, TaC, TaCN, TaSiN, Mn, Zr, TiN, TaN, Ru, Mo, Al, WN, Cu, W, Re, Ir, Co, Ni, other suitable metal materials or a combination thereof. In various embodiments, the gate electrode layer **274** of the HK MG stack **270** may be formed by ALD, PVD, CVD, e-beam evaporation, or other suitable process. Further, the gate electrode layer **274** may be formed separately for N-FET and P-FET transistors which may use different metal layers (e.g., for providing an N-type or P-type work function).

Referring to FIG. **20C**, in the illustrated embodiment, the HK MG stack **270** straddles the middle dielectric fin **228** due to the prior removal of its high-k dielectric layer **230** and engages two stacks of channel members **208** on both sides of the middle dielectric fin **228**, such that two transistors share the same gate stack. The HK MG stack **270** is also referred to as a joint gate stack in such a configuration. The HK MG stack **270** may be etched back so that the top surface of the HK MG stack **270** is lower than the top surface of the high-k dielectric layer **230** of other dielectric fins **228** on both sides of the HK MG stack **270**, for example, about 2 nm to about 10 nm lower. The dielectric fins **228** on both sides of the HK MG stack **270** function as gate isolation features that isolate the HK MG stack **270** from other adjacent gate stacks. The portion of the etched-back HK MG stack **270** above the top epitaxial layer **208** may have a thickness ranging from about 10 nm to about 20 nm.

After the etching back of the HK MG stack **270**, a self-aligned cap (SAC) layer **278** is deposited over the device **200** by CVD, PECVD, or a suitable deposition process. The SAC layer **278** may include silicon oxide, silicon nitride, silicon carbide, silicon carbonitride, silicon oxynitride, silicon oxycarbonitride, aluminum oxide, aluminum nitride, aluminum oxynitride, zirconium oxide, zirconium nitride, zirconium aluminum oxide, hafnium oxide, or a suitable dielectric material. In various embodiments, a CMP process may be performed to remove excessive metal from the SAC layer **278**, and thereby provide a substantially planar top surface of the device **200**.

The device **200** may undergo further processing to form various features and regions known in the art. For example, subsequent processing may form contact openings, contact metal, as well as various contacts/vias/lines and multilayers interconnect features (e.g., metal layers and interlayer dielectrics), configured to connect the various features to form a functional circuit that may include one or more multi-gate devices. In furtherance of the example, a multi-layer interconnection may include vertical interconnects, such as vias or contacts, and horizontal interconnects, such as metal lines. The various interconnection features may employ various conductive materials including copper, tungsten, and/or silicide. In one example, a damascene and/or dual damascene process is used to form a copper related multilayer interconnection structure. Moreover, additional process steps may be implemented before, during, and

after the method **100**, and some process steps described above may be replaced or eliminated in accordance with various embodiments of the method **100**.

Although not intended to be limiting, one or more embodiments of the present disclosure provide many benefits to a semiconductor device and the formation thereof. For example, embodiments of the present disclosure provide dielectric fins for improving fin uniformity and defining space for source/drain (S/D) features, and sacrificial cladding layers for reserving space for metal gate stacks. The removal of the sacrificial cladding layers prior to the forming of dummy gate structures allows less etching of a base portion of the semiconductor fins underneath the S/D features, which in turn suppresses substrate leakage current. The removal of the sacrificial cladding layers prior to the forming of dummy gate structures also increases the uniformity of inner spacer dimensions and reduces risks of over etching channel members during the channel member release process. Furthermore, the dielectric fin and sacrificial cladding layer formation method can be easily integrated into existing semiconductor fabrication processes.

In one exemplary aspect, the present disclosure is directed to a method. The method includes forming a semiconductor fin protruding from a substrate, forming a cladding layer on sidewalls of the semiconductor fin, forming first and second dielectric fins sandwiching the semiconductor fin, removing the cladding layer, thereby forming trenches between the semiconductor fin and the first and second dielectric fins, after the removing of the cladding layer, forming a dummy gate structure over the semiconductor fin and in the trenches, recessing the semiconductor fin in a region proximal to the dummy gate structure, a top surface of the recessed semiconductor fin in the region having a concave shape, forming an epitaxial feature on the recessed semiconductor fin, and forming a metal gate stack replacing the dummy gate structure. In some embodiments, the method further includes forming an isolation feature on the substrate. The semiconductor fin protrudes through the isolation feature. After the removing of the cladding layer, the trenches expose the isolation feature. In some embodiments, a bottom portion of the dummy gate structure in the trenches is in contact with the isolation feature. In some embodiments, the top surface of the recessed semiconductor fin in the region is above the isolation feature. In some embodiments, the method further includes depositing gate sidewall spacers on sidewalls of the dummy gate structure and in the trenches. In some embodiments, a bottom surface of the epitaxial feature is below a top surface of the recessed semiconductor fin in the region. In some embodiments, the forming of the epitaxial feature defines voids positioned laterally between the semiconductor fin and the first and second dielectric fins and vertically between the epitaxial feature and the substrate. In some embodiments, the cladding layer includes amorphous or polycrystalline semiconductor material. In some embodiments, the semiconductor material is silicon germanium. In some embodiments, the semiconductor fin includes a plurality of sacrificial layers and a plurality of channel layers alternately arranged, and the method further includes laterally recessing end portions of the sacrificial layers, thereby forming cavities, and forming inner spacers in the cavities, the inner spacers interposing the epitaxial feature and the metal gate stack.

In another exemplary aspect, the present disclosure is directed to a method. The method includes forming a stack of first type and second type epitaxial layers on a semiconductor substrate, the first type and second type epitaxial layers having different material compositions and the first

19

type and second type epitaxial layers being alternately disposed in a vertical direction, patterning the stack and a top portion of the semiconductor substrate to form a fin, depositing a sacrificial layer on a sidewall of the fin, forming a dielectric pillar on a sidewall of the sacrificial layer, etching the sacrificial layer, thereby exposing a bottom second type epitaxial layer, after the etching of the sacrificial layer, depositing a sacrificial structure over the fin and the dielectric pillar, the sacrificial structure being in contact with the bottom second type epitaxial layer, removing the sacrificial structure and the second type epitaxial layers, thereby forming a trench, and depositing a conductive feature in the trench and wrapping around the first type epitaxial layers. In some embodiments, the second type epitaxial layers and the sacrificial layer include a same semiconductor material. In some embodiments, the semiconductor material is silicon germanium, and germanium concentration is different in the second type epitaxial layers and the sacrificial layer. In some embodiments, the dielectric pillar includes a lower portion of a first dielectric material and an upper portion of a second dielectric material different from the first dielectric material, the method further includes recessing the sacrificial structure to expose the upper portion of the dielectric pillar, and prior to the depositing of the conductive feature, removing the upper portion of the dielectric pillar. In some embodiments, the method further includes recessing the fin in a region proximal to the sacrificial structure, such that the stack is removed from the region and a top surface of the top portion of the semiconductor substrate is exposed in the region, the top surface of the top portion of the semiconductor substrate in the region being above a bottom surface of the dielectric pillar. In some embodiments, the method further includes epitaxially growing a semiconductor feature from the top surface of the top portion of the semiconductor substrate, a bottommost portion of the semiconductor feature being below the top surface of the top portion of the semiconductor substrate. In some embodiments, the method further includes depositing a dielectric layer on sidewalls of the sacrificial structure, the dielectric layer being in contact with the bottom second type epitaxial layer.

In yet another exemplary aspect, the present disclosure is directed to a multi-gate semiconductor device. The multi-gate semiconductor device includes an isolation feature disposed over a substrate, a top portion of the substrate protruding through the isolation feature, channel members disposed over the substrate, first and second dielectric features disposed over the isolation feature and sandwiching the channel members, an epitaxial feature abutting the channel members and directly above a top surface of the top portion of the substrate, the top surface of the top portion of the substrate being above the isolation feature, and a gate structure engaging the channel members. In some embodiments, a bottommost portion of the epitaxial feature is above the isolation feature. In some embodiments, a top surface of the first dielectric feature is above a top surface of the second dielectric feature, and the gate structure covers the top surface of the second dielectric feature.

The foregoing outlines features of several embodiments so that those of ordinary skill in the art may better understand the aspects of the present disclosure. Those of ordinary skill in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those of ordinary skill in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present

20

disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

What is claimed is:

1. A method, comprising:

forming a semiconductor fin protruding from a substrate; forming an isolation feature on the substrate, wherein the semiconductor fin protrudes through the isolation feature;

after the forming of the isolation feature, forming a cladding layer on sidewalls of the semiconductor fin, wherein the cladding layer and the isolation feature include different material compositions;

forming first and second dielectric fins sandwiching the semiconductor fin;

removing the cladding layer, thereby forming trenches between the semiconductor fin and the first and second dielectric fins;

after the removing of the cladding layer, forming a dummy gate structure over the semiconductor fin and in the trenches;

depositing gate sidewall spacers on sidewalls of the dummy gate structure and in the trenches;

recessing the semiconductor fin in a region proximal to the dummy gate structure, wherein a top surface of the recessed semiconductor fin in the region has a concave shape;

forming an epitaxial feature on the recessed semiconductor fin; and

forming a metal gate stack replacing the dummy gate structure.

2. The method of claim 1,

wherein after the removing of the cladding layer, the trenches expose the isolation feature.

3. The method of claim 1, wherein a bottom portion of the dummy gate structure in the trenches is in contact with the isolation feature.

4. The method of claim 1, wherein the top surface of the recessed semiconductor fin in the region is above the isolation feature.

5. The method of claim 1, wherein a bottom surface of the epitaxial feature is below a top surface of the recessed semiconductor fin in the region.

6. The method of claim 1, wherein the forming of the epitaxial feature defines voids positioned laterally between the semiconductor fin and the first and second dielectric fins and vertically between the epitaxial feature and the substrate.

7. The method of claim 1, wherein the cladding layer includes amorphous or polycrystalline semiconductor material.

8. The method of claim 7, wherein the semiconductor material is silicon germanium.

9. The method of claim 1, wherein the semiconductor fin includes a plurality of sacrificial layers and a plurality of channel layers alternately arranged, the method further comprising:

laterally recessing end portions of the sacrificial layers, thereby forming cavities; and

forming inner spacers in the cavities, wherein the inner spacers interpose the epitaxial feature and the metal gate stack.

10. A method, comprising:

forming a stack of first type and second type epitaxial layers on a semiconductor substrate, the first type and second type epitaxial layers having different material

21

compositions and the first type and second type epitaxial layers being alternately disposed in a vertical direction;

patterning the stack and a top portion of the semiconductor substrate to form a fin;

forming an isolation feature on the semiconductor substrate such that the fin protrudes from the isolation feature;

depositing a sacrificial layer over a top surface of the isolation feature and on a sidewall of the fin;

forming a dielectric pillar on a sidewall of the sacrificial layer;

etching the sacrificial layer, thereby exposing a bottom second type epitaxial layer and the top surface of the isolation feature;

after the etching of the sacrificial layer, depositing a sacrificial structure over the fin and the dielectric pillar, wherein the sacrificial structure is in contact with the bottom second type epitaxial layer;

removing the sacrificial structure and the second type epitaxial layers, thereby forming a trench; and

depositing a conductive feature in the trench and wrapping around the first type epitaxial layers.

11. The method of claim 10, wherein the second type epitaxial layers and the sacrificial layer include a same semiconductor material.

12. The method of claim 11, wherein the semiconductor material is silicon germanium, and wherein germanium concentration is different in the second type epitaxial layers and the sacrificial layer.

13. The method of claim 10, wherein the dielectric pillar includes a lower portion of a first dielectric material and an upper portion of a second dielectric material different from the first dielectric material, the method further comprising:

recessing the sacrificial structure to expose the upper portion of the dielectric pillar; and

prior to the depositing of the conductive feature, removing the upper portion of the dielectric pillar.

14. The method of claim 10, further comprising:

recessing the fin in a region proximal to the sacrificial structure, such that the stack is removed from the region and a top surface of the top portion of the semiconductor substrate is exposed in the region,

22

wherein the top surface of the top portion of the semiconductor substrate in the region is above a bottom surface of the dielectric pillar.

15. The method of claim 14, further comprising:

epitaxially growing a semiconductor feature from the top surface of the top portion of the semiconductor substrate,

wherein a bottommost portion of the semiconductor feature is below the top surface of the top portion of the semiconductor substrate.

16. The method of claim 10, further comprising:

depositing a dielectric layer on sidewalls of the sacrificial structure, wherein the dielectric layer is in contact with the bottom second type epitaxial layer.

17. A multi-gate semiconductor device, comprising:

an isolation feature disposed over a substrate, wherein a top portion of the substrate protrudes through the isolation feature;

channel members disposed over the substrate;

first and second dielectric features disposed over the isolation feature and sandwiching the channel members, wherein bottom surfaces of the first and second dielectric features are above a topmost surface of the isolation feature;

an epitaxial feature abutting the channel members and directly above a top surface of the top portion of the substrate, wherein the top surface of the top portion of the substrate is above the isolation feature, and wherein a bottom surface of the epitaxial feature is spaced apart from a top surface of the isolation feature such that an air gap is trapped therebetween; and

a gate structure engaging the channel members.

18. The multi-gate semiconductor device of claim 17, wherein a bottommost portion of the epitaxial feature is above the isolation feature.

19. The multi-gate semiconductor device of claim 17, wherein a top surface of the first dielectric feature is above a top surface of the second dielectric feature, and wherein the gate structure covers the top surface of the second dielectric feature.

20. The multi-gate semiconductor device of claim 17, wherein the epitaxial feature is free of contact with the isolation feature.

* * * * *