

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408542
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Jo; Yongjun et al.

Display panel and method of manufacturing the same

Abstract

A display panel includes a substrate including an opening and a display area surrounding the opening, a light-emitting element in the display area and including a first electrode, an intermediate layer, and a second electrode, a multi-layered dam in a non-display area between the opening and the display area, an encapsulation layer extending substantially over the display area and the non-display area, and a first layer pattern disposed in one area of the non-display area.

Inventors: Jo; Yongjun (Yongin-si, KR), Jung; Kwangchul (Yongin-si, KR), Kim; Mina (Yongin-si, KR), Lee; Seulbee (Yongin-si, KR)

Applicant: Samsung Display Co., Ltd. (Yongin-si, KR)

Family ID: 81185645

Assignee: Samsung Display Co., LTD. (Gyeonggi-do, KR)

Appl. No.: 18/404862

Filed: January 04, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240244942 A1	Jul. 18, 2024

Foreign Application Priority Data

KR	10-2020-0135811	Oct. 20, 2020
----	-----------------	---------------

Related U.S. Application Data

division parent-doc US 17468526 20210907 US 11889744 child-doc US 18404862

Publication Classification

Int. Cl.: **H10K71/20** (20230101); **H10K50/844** (20230101); **H10K59/12** (20230101); **H10K59/65** (20230101); **H10K59/80** (20230101); **H10K71/00** (20230101); H10K59/131 (20230101)

U.S. Cl.:

CPC **H10K71/221** (20230201); **H10K50/844** (20230201); **H10K59/12** (20230201); **H10K59/65** (20230201); **H10K59/80517** (20230201); **H10K71/00** (20230201); **H10K71/621** (20230201); H10K59/1201 (20230201); H10K59/131 (20230201); H10K59/8731 (20230201)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10362696	12/2018	Ahn	N/A	N/A
10649567	12/2019	Kim	N/A	H10K 59/873
10840317	12/2019	Oh et al.	N/A	N/A
2016/0285038	12/2015	Kim	N/A	H10K 59/8731
2019/0074459	12/2018	Kim et al.	N/A	N/A
2020/0303677	12/2019	Lee	N/A	H10K 59/124
2020/0321292	12/2019	Park	N/A	H10K 59/131
2021/0026477	12/2020	Lee	N/A	G06F 3/0412
2021/0111231	12/2020	Choi et al.	N/A	N/A
2021/0265429	12/2020	Yamanaka	N/A	H05B 33/02

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
110649180	12/2019	CN	N/A
10-2016-0057197	12/2015	KR	N/A
10-2017-0045459	12/2016	KR	N/A
10-2018-0114565	12/2017	KR	N/A
10-2020-0102580	12/2019	KR	N/A

OTHER PUBLICATIONS

Notice of Allowance issued Oct. 2, 2023, in U.S. Appl. No. 17/468,526. cited by applicant

Primary Examiner: Mandala; Michelle

Attorney, Agent or Firm: HARNESS, DICKEY & PIERCE, P.L.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a Divisional of U.S. patent application Ser. No. 17/468,526, filed Sep. 7, 2021, which claims priority from and the benefit of Korean Patent Application No. 10-2020-0135811, filed on Oct. 20, 2020, each of which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND

Field

(1) Embodiments of the invention relate generally to a display apparatus and, more specifically to a display panel having an opening formed in a display area of the display panel and a method of manufacturing the same.

Discussion of the Background

(2) Generally, a display apparatus may be used in a mobile device, such as a smartphone, a laptop computer, a digital camera, a camcorder, a portable information terminal, a notebook, or a tablet personal computer, or in an electronic device such as a desktop computer, a television, an outdoor billboard, a display apparatus for exhibition, a dashboard for a vehicle, or a head-up display (HUD).

(3) Recently, in a display apparatus, the trend in the industry is to increase the size of the display area that displays images. Various functions connected to a display apparatus have been added while the area occupied by a display area has increased. An opening may be formed in the display area to add various functions.

(4) The above information disclosed in this Background section is only for understanding of the background of the inventive concepts, and, therefore, it may contain information that does not constitute prior art.

SUMMARY

(5) Applicant discovered that during manufacturing of an opening in a display panel, particles may be generated when forming a non-display area around the opening area. The particles may cause a crack in an encapsulation layer, which may damage a light-emitting element surrounding the opening.

(6) Display panels constructed according to the principles and embodiments of the invention and illustrative methods of manufacturing the same are capable of readily controlling particles that may be generated during the process of making a hole in the display panel. For example, a 2-step Laser Lift Off (LLO) method may be used to remove a sacrificial layer, an intermediate layer, and a second electrode, which are stacked in the non-display area around the opening without generating significant accumulation of harmful particles.

(7) Additional features of the inventive concepts will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the inventive concepts.

(8) According to one aspect of the invention, a method of manufacturing a display panel having an opening, a display area surrounding the opening, and a non-display area between the opening and the display area, the method includes the steps of: forming a pixel circuit including a at least one thin-film transistor in the display area, forming a first electrode electrically connected to the at least one thin-film transistor, forming a first layer having a plurality of slits in the non-display area, forming, on the first electrode, an intermediate layer and a second electrode that form a light-emitting element, the intermediate layer and the second electrode being disposed on the display area and the non-display area, and covering the first layer, lifting the second electrode off from the intermediate layer by irradiating a first laser beam having a first energy density toward the first layer, the intermediate layer, and the second electrode, which are stacked, and lifting off the first layer and the intermediate layer by irradiating a second laser beam having a second energy density greater than the first energy density toward the first layer.

(9) The first layer may include a sacrificial layer formed in the same process as that of the first

electrode and including a same material as that of the first electrode.

(10) The sacrificial layer may include a multi-layered structure of indium tin oxide (ITO)/silver (Ag)/ITO.

(11) The plurality of slits may be formed over substantially an entire area of the first layer.

(12) The plurality of slits may be formed in i) a discontinuous linear pattern or a discontinuous curved pattern or ii) a continuous linear pattern or a continuous curved pattern.

(13) The second electrode may include a metal material including Ag.

(14) In the step of irradiating the first laser beam, the first laser beam may pass through the plurality of slits formed in the first layer and then pass through the intermediate layer to be irradiated onto one surface of the second electrode.

(15) The first energy density may be about 0.7 J/cm.² or less.

(16) In the step of irradiating the second laser beam, the second laser beam may be irradiated to one surface of the first layer in which the plurality of slits are formed.

(17) The second energy density may be about 1.5 J/cm.² or more.

(18) The method may further include the step of forming a pattern in a portion of the first layer disposed in at least one non-display area around a start point or a finish point where the laser beam is irradiated.

(19) The method may further include the step of forming a multi-layered dam in the non-display area in the same process as that of a plurality of insulating layers among insulating layers between each element of the thin-film transistor and the light-emitting element. A vicinity of the start point where the laser beam is irradiated may correspond to the non-display area adjacent to the dam, and the pattern in the first layer may be located in the non-display area adjacent to the dam.

(20) A vicinity of the finish point where the laser beam is irradiated may correspond to the non-display area adjacent to the opening, and the pattern in the first layer may be located in the non-display area adjacent to the opening.

(21) The method may further include the step of forming an encapsulation layer over the display area and the non-display area. At least one inorganic encapsulation layer in the encapsulation layer may extend to an area from which the first layer is lifted off to cover the pattern in the first layer.

(22) According to another aspect of the invention, a display panel includes: a substrate including an opening and a display area surrounding the opening, a light-emitting element in the display area and including a first electrode, an intermediate layer, and a second electrode, a multi-layered dam in a non-display area between the opening and the display area, an encapsulation layer extending substantially over the display area and the non-display area, and a first layer pattern disposed in one area of the non-display area.

(23) The first layer pattern may be disposed in at least one of the non-display area adjacent to the multi-layered dam or the non-display area adjacent to the opening.

(24) The first layer pattern may be arranged in the one area of the non-display area in a discontinuous linear pattern or a discontinuous curved pattern.

(25) The first layer pattern may be arranged in the one area of the non-display area in a continuous linear pattern or a continuous curved pattern.

(26) The first layer pattern may include a sacrificial layer pattern having the same material as that of the first electrode.

(27) At least one inorganic encapsulation layer in the encapsulation layer may cover the first layer pattern.

(28) It is to be understood that both the foregoing general description and the following detailed description are illustrative and explanatory and are intended to provide further explanation of the invention as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention, and together with the description serve to explain the inventive concepts.
- (2) FIG. 1 is a perspective view of an embodiment of a display apparatus constructed according to the principles of the invention.
- (3) FIG. 2 is a cross-sectional view taken along line II-II' of FIG. 1.
- (4) FIG. 3 is a plan view of an embodiment of a display panel included in the display apparatus of FIG. 1.
- (5) FIG. 4 is an equivalent circuit diagram of an embodiment of a representative pixel of the display panel of FIG. 3.
- (6) FIG. 5 is an enlarged plan view of signal lines in a first non-display area of the display panel of FIG. 3.
- (7) FIG. 6 is an enlarged plan view of an area of the display panel of FIG. 3. adjacent to the first non-display area
- (8) FIGS. 7A and 7B are cross-sectional views of embodiments taken along line VII-VII' of FIG. 6.
- (9) FIG. 8 is a cross-sectional view taken along line VIII-VIII' of FIG. 6.
- (10) FIGS. 9A to 9E are cross-sectional views sequentially showing an illustrative method of manufacturing the display panel shown in FIG. 8.
- (11) FIGS. 10A to 10D are plan views of embodiments of a sacrificial layer shown in
- (12) FIG. 9A illustrating various patterns of slits in the sacrificial layer.
- (13) FIGS. 11A to 11C are cross-sectional views sequentially showing an illustrative operation of removing a sacrificial layer, a functional layer, and a second electrode, which are stacked, as shown in FIG. 9B, by irradiating a laser beam.

DETAILED DESCRIPTION

- (14) In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various embodiments or implementations of the invention. As used herein “embodiments” and “implementations” are interchangeable words that are non-limiting examples of devices or methods employing one or more of the inventive concepts disclosed herein. It is apparent, however, that various embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various embodiments. Further, various embodiments may be different, but do not have to be exclusive. For example, specific shapes, configurations, and characteristics of an embodiment may be used or implemented in another embodiment without departing from the inventive concepts.
- (15) Unless otherwise specified, the illustrated embodiments are to be understood as providing features of varying detail of some ways in which the inventive concepts may be implemented in practice. Therefore, unless otherwise specified, the features, components, modules, layers, films, panels, regions, and/or aspects, etc. (hereinafter individually or collectively referred to as “elements”), of the various embodiments may be otherwise combined, separated, interchanged, and/or rearranged without departing from the inventive concepts.
- (16) The use of cross-hatching and/or shading in the accompanying drawings is generally provided to clarify boundaries between adjacent elements. As such, neither the presence nor the absence of cross-hatching or shading conveys or indicates any preference or requirement for particular materials, material properties, dimensions, proportions, commonalities between illustrated elements, and/or any other characteristic, attribute, property, etc., of the elements, unless specified. Further, in the accompanying drawings, the size and relative sizes of elements may be exaggerated for clarity and/or descriptive purposes. When an embodiment may be implemented differently, a

specific process order may be performed differently from the described order. For example, two consecutively described processes may be performed substantially at the same time or performed in an order opposite to the described order. Also, like reference numerals denote like elements.

(17) When an element, such as a layer, is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. To this end, the term “connected” may refer to physical, electrical, and/or fluid connection, with or without intervening elements. Further, the D1-axis, the D2-axis, and the D3-axis are not limited to three axes of a rectangular coordinate system, such as the x, y, and z-axes, and may be interpreted in a broader sense. For example, the D1-axis, the D2-axis, and the D3-axis may be perpendicular to one another, or may represent different directions that are not perpendicular to one another. For the purposes of this disclosure, “at least one of X, Y, and Z” and “at least one selected from the group consisting of X, Y, and Z” may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, XYY, YZ, and ZZ. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

(18) Although the terms “first,” “second,” etc. may be used herein to describe various types of elements, these elements should not be limited by these terms. These terms are used to distinguish one element from another element. Thus, a first element discussed below could be termed a second element without departing from the teachings of the disclosure.

(19) Spatially relative terms, such as “beneath,” “below,” “under,” “lower,” “above,” “upper,” “over,” “higher,” “side” (e.g., as in “sidewall”), and the like, may be used herein for descriptive purposes, and, thereby, to describe one elements relationship to another element(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

(20) The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. Moreover, the terms “comprises,” “comprising,” “includes,” and/or “including,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. It is also noted that, as used herein, the terms “substantially,” “about,” and other similar terms, are used as terms of approximation and not as terms of degree, and, as such, are utilized to account for inherent deviations in measured, calculated, and/or provided values that would be recognized by one of ordinary skill in the art.

(21) Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

(22) FIG. 1 is a perspective view of an embodiment of a display apparatus 1 constructed according to the principles of the invention.

(23) Referring to FIG. 1, the display apparatus 1 includes a display area DA which emits light and a

non-display area NDA which does not emit light. The non-display area NDA may be adjacent to the display area DA. The display apparatus **1** may provide certain images by using light emitted from a plurality of pixels in the display area DA.

(24) The display apparatus **1** includes an opening area OA which is at least partially surrounded by the display area DA. As an embodiment, the opening area OA may be entirely surrounded by the display area DA.

(25) The non-display area NDA may include a first non-display area NDA1 surrounding the opening area OA and a second non-display area NDA2 surrounding the periphery of the display area DA. The first non-display area NDA1 may entirely surround the opening area OA, the display area DA may entirely surround the first non-display area NDA1, and the second non-display area NDA2 may entirely surround the display area DA.

(26) Hereinafter, the display apparatus **1** is described as an organic light-emitting display apparatus as an example, but is not limited thereto. As another embodiment, the display apparatus **1** may include an inorganic light-emitting display apparatus, a quantum dot light-emitting display apparatus, or the like.

(27) FIG. **2** is a cross-sectional view of the display apparatus **1** taken along line II-II' of FIG. **1**.

(28) Referring to FIG. **2**, the display apparatus **1** may include a display panel **10**, an input sensing member **20** on the display panel **10**, and an optical functional member **30**. The display panel **10**, the input sensing member **20**, and the optical functional member **30** may be covered by a window **40**.

The display apparatus **1** may take the form of or be incorporated into various electronic devices such as a smart phone, a notebook computer, and a smart watch, as some non-limiting examples.

(29) The display panel **10** may display an image. The display panel **10** includes a plurality of pixels in the display area DA. The plurality of pixels may include a light-emitting element and a pixel circuit connected thereto. The light-emitting element may include an organic light-emitting diode, an inorganic light-emitting diode, a quantum dot light-emitting diode, or the like.

(30) The input sensing member **20** may obtain coordinate information according to an external input, for example, a touch event. The input sensing member **20** may include a sensing electrode and a trace line connected to the sensing electrode. The input sensing member **20** may be arranged on the display panel **10**.

(31) The input sensing member **20** may be directly formed on the display panel **10**, or may be separately formed and then adhered to the display panel **10** through an optical clear adhesive (OCA). For example, the input sensing member **20** may be continuously formed after an operation of forming the display panel **10**, and in this case, an adhesive layer may not be between the input sensing member **20** and the display panel **10**. Although the input sensing member **20** is illustrated as being between the display panel **10** and the optical functional member **30**, as another embodiment, the input sensing member **20** may be on the optical functional member **30**.

(32) The optical functional member **30** may include an anti-reflection layer. The anti-reflection layer may reduce the reflectance of external light incident from the outside toward the display panel **10** through the window **40**. The anti-reflection layer may include a retarder and a polarizer. The retarder may be a film type or a liquid-crystal coating type, and may include a $\lambda/2$ retarder and/or a $\lambda/4$ retarder. The polarizer may also be a film type or a liquid-crystal coating type. The film-type polarizer may include a stretch-type synthetic resin film, and the liquid-crystal-coating-type polarizer may include a plurality of liquid-crystals having a certain arrangement. The retarder and the polarizer may further include a protective film. The retarder and the polarizer or the protective film may be defined as a base layer of the anti-reflection layer.

(33) As another embodiment, the anti-reflection layer may include a black matrix and color filters. The color filters may be arranged considering a color of light emitted from each of the plurality of pixels. As another embodiment, the anti-reflection layer may include a destructive interference structure. The destructive interference structure may include a first reflective layer and a second reflective layer which are on different layers. First reflected light and second reflected light

respectively reflected from the first reflective layer and the second reflective layer may destructively interfere, and thus, the reflectance of external light may be reduced.

(34) The optical functional member **30** may include a lens layer. The lens layer may improve light emission efficiency of light emitted from the display panel **10** or reduce color deviation. The lens layer may include a layer having a concave or convex lens shape, or may include a plurality of layers having different refractive indices. The optical functional member **30** may include all of the anti-reflection layer and the lens layer, or may include any one of the anti-reflection layer and the lens layer.

(35) The display panel **10**, the input sensing member **20**, and the optical functional member **30** may include openings. In detail, the display panel **10**, the input sensing member **20**, and the optical functional member **30** may respectively include first to third openings **10H**, **20H**, and **30H**. The first to third openings **10H**, **20H**, and **30H** may overlap each other. The first to third openings **10H**, **20H**, and **30H** may correspond to the opening area OA. As another embodiment, at least one of the display panel **10**, the input sensing member **20**, and the optical functional member **30** may not include an opening.

(36) A component **50** may be received in the opening area OA. The component **50** may be located in the first to third openings as shown by a solid line, or may be below the display panel **10** as shown by a dotted line.

(37) The component **50** may include an electronic element such as an electronic element using light or sound. The electronic element may include a sensor receiving and using light, such as an infrared sensor, a camera capturing an image by receiving light, a sensor outputting and sensing light or sound to measure a distance or recognize a fingerprint or the like, a small lamp outputting light, a speaker outputting sound, or the like.

(38) An electronic element using light may use light of various wavelengths, such as visible light, infrared light, ultraviolet light, or the like. As an embodiment, the opening area OA may be understood as a transmission area through which light or sound output from the component **50** to the outside or from the outside toward the electronic element may pass.

(39) As another embodiment, when the display apparatus **1** is used as a smart watch or an instrument panel for vehicles, the component **50** may be a member including the hand of a clock, a needle indicating certain information (for example, speed of a vehicle, or the like), or the like. When the display apparatus **1** includes the hand of a clock or the instrument panel for vehicles, a portion of the component **50** may be exposed to the outside through the window **40**, and the window **40** may include an opening corresponding to the opening area OA.

(40) The component **50** may include a component associated with a function of the display panel **10**, or may include a component such as accessories that increase aesthetics of the display panel **10**.

(41) FIG. **3** is a plan view of an embodiment of a display panel **10** included in the display apparatus of FIG. **1**, and FIG. **4** is an equivalent circuit diagram of an embodiment of a representative pixel of the display panel **10** of FIG. **3**.

(42) Referring to FIGS. **3** and **4**, the display panel **10** includes the display area DA and the first and second non-display areas NDA1 and NDA2. A substrate **100** of FIG. **3** may be understood as a substrate provided in the display panel **10**. For example, the substrate **100** may be understood as including the opening area OA, the display area DA, the first and second non-display areas NDA1 and NDA2.

(43) The display panel **10** includes a plurality of pixels P in the display area DA. As shown in FIG. **4**, each of the plurality of pixels P includes a pixel circuit PC and an organic light-emitting diode OLED as a light-emitting element connected to the pixel circuit PC. The pixel circuit PC may include a driving thin-film transistor T1, a switching thin-film transistor T2, and a storage capacitor Cst. Each pixel P may emit, for example, red, green, blue, or white light through the organic light-emitting diode OLED.

(44) Referring to FIG. **4**, the switching thin-film transistor T2 may be connected to a scan line SL

and a data line DL, and be configured to deliver, to the driving thin-film transistor T1, a data voltage input from the data line DL based on a switching voltage input from the scan line SL. The storage capacitor Cst may be connected to the switching thin-film transistor T2 and a driving voltage line PL, and store a voltage corresponding to a difference between a voltage received from the switching thin-film transistor T2 and a first power supply voltage ELVDD supplied to the driving voltage line PL.

(45) The driving thin-film transistor T1 may be connected to the driving voltage line PL and the storage capacitor Cst and may control a driving current flowing from the driving voltage line PL to the organic light-emitting diode OLED in accordance with a voltage value stored in the storage capacitor Cst.

(46) The organic light-emitting diode OLED may emit light having a certain brightness according to the driving current. A second electrode (for example, a cathode) of the organic light-emitting diode OLED may receive a second power supply voltage ELVSS.

(47) Although FIG. 4 describes that the pixel circuit PC includes two thin-film transistors and one storage capacitor, the embodiments are not limited thereto. The number of thin-film transistors and the number of storage capacitors may be variously changed according to the design of the pixel circuit PC.

(48) Referring to FIG. 3 again, the first non-display area NDA1 may surround the opening area OA. The first non-display area NDA1 may be an area without a light-emitting element such as an organic light-emitting diode configured to emit light.

(49) Signal lines (e.g., data lines DL and scan lines SL shown in FIG. 5) providing signals to the plurality of pixels P located around the opening area OA may pass by the first non-display area NDA1. A scan driver 1100 providing a scan signal to each of the plurality of pixels P, a data driver 1200 providing a data signal to each of the plurality of pixels P, a main power-supply wiring configured to provide first and second power-supply voltages, or the like may be arranged in the second non-display area NDA2. As an embodiment, the data driver 1200 is illustrated as being arranged at a lower end of the substrate 100, but as another embodiment, the data driver 1200 may be arranged on a flexible printed circuit board (FPCB) electrically connected to a pad arranged at a lower end of the display panel 10.

(50) FIG. 5 is an enlarged plan view of signal lines in the first non-display area NDA1 of the display panel of FIG. 3.

(51) Referring to FIG. 5, the plurality of pixels P may be arranged in the display area DA around the opening area OA, and the first non-display area NDA1 may be located between the opening area OA and the display area DA.

(52) The plurality of pixels P may be apart from each other around the opening area OA. The plurality of pixels P may be vertically spaced apart from each other around the opening area OA, or may be horizontally spaced apart from each other around the opening area OA.

(53) Signal lines adjacent to the opening area OA among signal lines supplying signals to the plurality of pixels P may bypass the opening area OA. For example, among data lines DL passing by the display area DA, some data lines DL may extend in a y-direction to provide data signals to the plurality of pixels P vertically arranged with the opening area OA therebetween, and may bypass an edge of the opening area OA in the first non-display area NDA1. Among scan lines SL passing by the display area DA, some scan lines SL may extend in an x-direction to provide scan signals to the plurality of pixels P horizontally arranged with the opening area OA therebetween, and may bypass the edge of the opening area OA in the first non-display area NDA1.

(54) FIG. 6 is an enlarged plan view of an area of the display panel of FIG. 3 adjacent to the first non-display area.

(55) Referring to FIG. 6, at least one dam 240 may be located between the opening area OA and the display area DA. A plurality of dams 240 apart from each other may be provided. The dam 240 may have a multi-layered structure. The dam 240 may be on one of insulating layers on the

substrate (**100** in FIG. 3). In the first non-display area **NDA1**, the dam **240** may have an annular shape that entirely surrounds the opening area **OA**. The inner diameter of the annular shape may be greater than the outer diameter of the opening area **OA**.

(56) A sacrificial layer area **SLA**, which is a non-display area between the dam **240** and the opening area **OA**, may be an area from which first and second functional layers **222a** and **222c** of an intermediate layer (**222** of FIG. 7A) including an organic material and a second electrode **223** are removed. The sacrificial layer area **SLA** may prevent penetration of foreign substances such as moisture or the like through the opening area **OA**. A sacrificial layer pattern **930** to be described below may be arranged in the sacrificial layer area **SLA**.

(57) FIG. 7A is a cross-sectional view of an embodiment of the pixel taken along line VII-VII' of FIG. 6.

(58) Referring to FIG. 7A, the pixel circuit **PC** and the organic light-emitting diode **OLED** electrically connected to the pixel circuit **PC** may be in the display area **DA**. The pixel circuit **PC** may be on the substrate **100**, and the organic light-emitting diode **OLED** may be on the pixel circuit **PC**.

(59) The substrate **100** may include a polymer resin or glass. As an embodiment, the substrate **100** may include a polymer resin such as polyethersulphone, polyacrylate, polyetherimide, polyethylene naphthalate, polyethylene terephthalate, polyphenylene sulfide, polyimide, polycarbonate, cellulose acetate propionate, or the like, and may be flexible. As another embodiment, the substrate **100** may include glass containing SiO_2 as a main component, or may include a resin such as reinforced plastic, and may be rigid.

(60) A buffer layer **201** may be formed on the substrate **100** to prevent impurities from penetrating into a first semiconductor layer **A1** of a first thin-film transistor **TFT**. The buffer layer **201** may include an inorganic material such as an oxide or a nitride, an organic material, or an organic and inorganic composite, and may be a single layer or a multi-layer. A barrier layer blocking penetration of external air may be further included between the substrate **100** and the buffer layer **201**. In some embodiments, the buffer layer **201** may include silicon oxide (SiO_2) or silicon nitride (Si_3N_4).

(61) The pixel circuit **PC** may be disposed on the buffer layer **201**. The pixel circuit **PC** includes the first thin-film transistor **TFT** and the storage capacitor **Cst**. The first thin-film transistor **TFT** may include the first semiconductor layer **A1**, a first gate electrode **G1**, a first source electrode **S1**, and a first drain electrode **D1**. The first thin-film transistor **TFT** may correspond to the driving thin-film transistor **T1** of FIG. 4.

(62) As an embodiment, the first thin-film transistor **TFT** is shown as a top-gate type in which the first gate electrode **G1** is above the first semiconductor layer **A1** with a first gate insulating layer **203** therebetween, but as another embodiment, the first thin-film transistor **TFT** may be a bottom-gate type.

(63) The first semiconductor layer **A1** may include polysilicon (Poly-Si). Alternatively, the first semiconductor layer **A1** may include amorphous-Si, an oxide semiconductor, an organic semiconductor, or the like. The first gate electrode **G1** may include a low-resistance metal material. The first gate electrode **G1** may include a conductive material including molybdenum (Mo), aluminum (Al), copper (Cu), titanium (Ti), or the like, and may be a single layer or a multi-layer.

(64) The first gate insulating layer **203** between the first semiconductor layer **A1** and the first gate electrode **G1** may include an inorganic insulating material such as silicon oxide (SiO_2), silicon nitride (Si_3N_4), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), titanium oxide (TiO_2), tantalum oxide (Ta_2O_5), hafnium oxide (HfO_2), zinc oxide (ZnO), or the like. The first gate insulating layer **203** may be a single layer or a multi-layer.

(65) The first source electrode **S1** and the first drain electrode **D1** may include a material having good conductivity. The first source electrode **S1** and the first drain electrode **D1** may include a conductive material including Mo, Al, Cu, Ti, or the like, and may be a single layer or a multi-

layer. As an embodiment, the first source electrode **S1** and the first drain electrode **D1** may be a multi-layer of Ti/Al/Ti.

(66) The storage capacitor **Cst** may include a lower electrode **CE1** and an upper electrode **CE2** which overlap each other with a second gate insulating layer **205** therebetween.

(67) The storage capacitor **Cst** may overlap the first thin-film transistor **TFT**. In detail, the first gate electrode **G1** of the first thin-film transistor **TFT** may be the lower electrode **CE1** of the storage capacitor **Cst**. As another embodiment, the storage capacitor **Cst** may not overlap the first thin-film transistor **TFT**.

(68) The upper electrode **CE2** of the storage capacitor **Cst** may include a conductive material including Mo, Al, Cu, Ti, or the like, and may be a single layer or a multi-layer.

(69) The second gate insulating layer **205** may perform the function of a dielectric layer of the storage capacitor **Cst**. The second gate insulating layer **205** may include an inorganic insulating material such as silicon oxide (SiO_2), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), titanium oxide (TiO_2), tantalum oxide (Ta_2O_5), hafnium oxide (HfO_2), zinc oxide (ZnO), or the like. The second gate insulating layer **205** may be a single layer or a multi-layer.

(70) An interlayer insulating layer **207** may cover the storage capacitor **Cst**. The interlayer insulating layer **207** may include an inorganic insulating material such as silicon oxide (SiO_2), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), titanium oxide (TiO_2), tantalum oxide (Ta_2O_5), hafnium oxide (HfO_2), zinc oxide (ZnO), or the like. The interlayer insulating layer **207** may be a single layer or a multi-layer.

(71) A planarization layer **209** may cover the pixel circuit **PC** including the first thin-film transistor **TFT** and the storage capacitor **Cst**. An upper surface of the planarization layer **209** may be a flat surface. The planarization layer **209** may include a general commercial polymer such as poly(methyl methacrylate) (**PMMA**) or polystyrene (**PS**), a polymer derivative having a phenol group, an acrylic polymer, an imide polymer, an aryl ether polymer, an amide polymer, a fluorine polymer, a p-xylene polymer, a vinyl alcohol polymer, a mixture thereof, or the like. As an embodiment, the planarization layer **209** may include polyimide. As another embodiment, the planarization layer **209** may include an inorganic insulating material, or may include an inorganic and organic insulating material.

(72) A first electrode **221** may be formed on the planarization layer **209**. The first electrode **221** may include a reflective film including silver (**Ag**), magnesium (**Mg**), aluminum (**Al**), platinum (**Pt**), palladium (**Pd**), gold (**Au**), nickel (**Ni**), neodymium (**Nd**), iridium (**Ir**), chromium (**Cr**), or a compound thereof. As another embodiment, the first electrode **221** may include a conductive oxide such as indium tin oxide (**ITO**), indium zinc oxide (**IZO**), zinc oxide (**ZnO**), indium oxide (In_2O_3), indium gallium oxide (**IGO**), and aluminum zinc oxide (**AZO**). As another embodiment, the first electrode **221** may further include a film including one of **ITO**, **IZO**, **ZnO**, and In_2O_3 above and below the reflective film. For example, the first electrode **221** may have a structure in which **ITO/Ag/ITO** are stacked. The first electrode **221** may include the same material as a sacrificial layer to be described below.

(73) A pixel defining film **211** may be formed on the first electrode **221**. The pixel defining film **211** may include an opening exposing an upper surface of the first electrode **221** and may cover an edge of the first electrode **221**. Accordingly, the pixel defining film **211** may define an emission area of a pixel. The pixel defining film **211** may include an organic insulating material. For example, the pixel defining film **211** may include an organic insulating material such as polyimide, polyamide, an acrylic resin, benzocyclobutene, hexamethyldisiloxane (**HMDSO**), a phenol resin, or the like, and may be formed in a spin coating method or the like.

(74) An intermediate layer **222** may be on an upper surface of the first electrode **221**. The intermediate layer **222** includes an emission layer **222b**. The intermediate layer **222** may include a first functional layer **222a** below the emission layer **222b** and a second functional layer **222c** on the emission layer **222b**. The emission layer **222b** may include a polymer organic material or a low-

molecular-weight organic material which emits light of a color.

(75) The first functional layer **222a** may be a single layer or a multi-layer. For example, when the first functional layer **222a** includes a polymer material, the first functional layer **222a** may be a hole transport layer (HTL) having a single-layered structure and may include poly-(3,4)-ethylene-dihydroxy thiophene (PEDOT) or polyaniline (PANI). When the first functional layer **222a** includes a low-molecular-weight material, the first functional layer **222a** may include a hole injection layer (HIL) and an HTL.

(76) The second functional layer **222c** may be omitted. For example, when the first functional layer **222a** and the emission layer **222b** include a polymer material, forming the second functional layer **222c** is preferable. The second functional layer **222c** may be a single layer or a multi-layer. The second functional layer **222c** may include an electron transport layer (ETL) or an electron injection layer (EIL).

(77) The emission layer **222b** may be arranged for each pixel in the display area DA. The emission layer **222b** may be arranged above the first electrode **221** exposed through the opening of the pixel defining film **211**. The first and second functional layers **222a** and **222c** provided in the intermediate layer **222** may extend from the display area DA to the first non-display area NDA1.

(78) A second electrode **223** may be on the intermediate layer **222**. The second electrode **223** may include a conductive material having a low work function. For example, the second electrode **223** may include a (semi)transparent layer including Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, lithium (Li), calcium (Ca), alloys thereof, or the like. As another embodiment, the second electrode **223** may further include a layer such as ITO, IZO, ZnO, In₂O₃ above the (semi)transparent layer including the above-stated material. The second electrode **223** may extend from the display area DA to the first non-display area NDA1. The intermediate layer **222** and the second electrode **223** may be formed by thermal deposition.

(79) A spacer **213** may be formed on the pixel defining film **211**. The spacer **213** may include an organic insulating material such as polyimide. The spacer **213** may include the same material as the pixel defining film **211**. In this case, the pixel defining film **211** and the spacer **213** may be formed together in a mask operation using a halftone mask or the like. As another embodiment, the spacer **213** may include a material different from that of the pixel defining film **211**.

(80) A capping layer **230** may be on the second electrode **223**. The capping layer **230** is a layer configured to protect the second electrode **223**, which may include an inorganic material or an organic material. As an embodiment, the capping layer **230** may be omitted.

(81) FIG. 7B is a cross-sectional view of another embodiment of the pixel taken along line VII-VII' of FIG. 6. In FIG. 7B, the same reference numerals as those in FIG. 7A denote the same or similar members, and thus, repetitive descriptions thereof will be omitted to avoid redundancy.

(82) Referring to FIG. 7B, the pixel circuit PC and the organic light-emitting diode OLED electrically connected to the pixel circuit PC may be in the display area DA. The pixel circuit PC may include the first thin-film transistor TFT including the first semiconductor layer A1 including polycrystalline silicon and a second thin-film transistor TFT_o including a second semiconductor layer A2 including an oxide semiconductor.

(83) The first thin-film transistor TFT may include the first semiconductor layer A1, the first gate electrode G1, the first source electrode S1, and the first drain electrode D1. The first thin-film transistor TFT is substantially the same as the first thin-film transistor TFT of FIG. 7A, and the first semiconductor layer A1 of the first thin-film transistor TFT may include polycrystalline silicon.

(84) Insulating layers of the illustrated embodiment include a first interlayer insulating layer **207a**, a second interlayer insulating layer **207b**, a first planarization layer **209a**, and a second planarization layer **209b**.

(85) As an embodiment, the substrate **100** may be a multi-layered structure. The substrate **100** may include a first base layer **101**, a first inorganic barrier layer **102**, a second base layer **103**, and a second inorganic barrier layer **104** which are sequentially stacked. Each of the first base layer **101**

and the second base layer **103** may include a polymer resin. Each of the first inorganic barrier layer **102** and the second inorganic barrier layer **104** may be a barrier layer that prevents penetration of foreign substances from the outside, which may include an inorganic material such as silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), and amorphous silicon (a-Si). Each of the first inorganic barrier layer **102** and the second inorganic barrier layer **104** may be a single layer or a multi-layer.

(86) The second thin-film transistor TFT_o may include a second semiconductor layer **A2**, a second gate electrode **G2**, a second source electrode **S2**, and a second drain electrode **D2**. In addition, the second thin-film transistor TFT_o may further include a lower gate electrode **G1** .

(87) The second semiconductor layer **A2** may be on the first interlayer insulating layer **207a**. In detail, the second semiconductor layer **A2** may be on a different layer from that of the first semiconductor layer **A1**. The second semiconductor layer **A2** may include a channel area, a source area, and a drain area, the source area and the drain area being respectively on both sides of the channel area.

(88) As an embodiment, the second semiconductor layer **A2** may include an oxide semiconductor. For example, the second semiconductor layer **A2** may include a zinc-oxide-based material, and may include Zn oxide, In—Zn oxide, Ga—In—Zn oxide, or the like. Alternatively, the second semiconductor layer **A2** may include an In—Ga—Zn—O (IGZO), In—Sn—Zn—O (ITZO), or In—Ga—Sn—Zn—O (IGTZO) semiconductor, which includes a metal such as In, Ga, and tin (Sn) in ZnO.

(89) The source area and the drain area of the second semiconductor layer **A2** may be formed by adjusting a carrier concentration of an oxide semiconductor to make the source area and the drain area conductive. For example, the source area and the drain area of the second semiconductor layer **A2** may be formed by increasing the carrier concentration through a plasma treatment using a hydrogen (H)-based gas, a fluorine (F)-based gas, or a combination thereof on the oxide semiconductor.

(90) The second gate electrode **G2** may overlap the channel area of the second semiconductor layer **A2**, and a third gate insulating layer **206** may be between the second semiconductor layer **A2** and the second gate electrode **G2**. In detail, the second gate electrode **G2** may be insulated from the second semiconductor layer **A2** by the third gate insulating layer **206**. The third gate insulating layer **206** may be formed on substantially the entire upper surface of the substrate **100**, but is not limited thereto. The third gate insulating layer **206** may be patterned according to a shape of the second gate electrode **G2**.

(91) The second gate electrode **G2** may include a conductive material including Mo, Al, Cu, Ti, or the like, and may be a single layer or a multi-layer. The second gate electrode **G2** may include a first layer **G2a** including Ti and a second layer **G2b** including Mo.

(92) The third gate insulating layer **206** may include an inorganic material including an oxide or a nitride. For example, the third gate insulating layer **206** may include silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al₂O₃), titanium oxide (TiO₂), tantalum oxide (Ta₂O₅), hafnium oxide (HfO₂), zinc oxide (ZnO), or the like. The second gate electrode **G2** may be on the third gate insulating layer **206**, include Mo, Cu, Ti, or the like, and be a single layer or a multi-layer.

(93) The lower gate electrode **G1** may be below the second semiconductor layer **A2** to overlap the channel area of the second semiconductor layer **A2**. The lower gate electrode **G1** may be on the same layer as the upper electrode **CE2** of the storage capacitor **Cst**. The first interlayer insulating layer **207a** may be between the lower gate electrode **G1** and the second semiconductor layer **A2**.

(94) The second interlayer insulating layer **207b** may cover the second gate electrode **G2** of the second thin-film transistor TFT_o. The second source electrode **S2** and the second drain electrode **D2** may be on the second interlayer insulating layer **207b**.

(95) The first interlayer insulating layer **207a** and the second interlayer insulating layer **207b** may

include an inorganic material including an oxide or a nitride. For example, the first interlayer insulating layer **207a** and the second interlayer insulating layer **207b** may include silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al₂O₃), titanium oxide (TiO₂), tantalum oxide (Ta₂O₅), hafnium oxide (HfO₂), zinc oxide (ZnO), or the like.

(96) The second source electrode **S2** and the second drain electrode **D2** may be respectively connected to the source area and the drain area of the second semiconductor layer **A2** through contact holes penetrating through the second interlayer insulating layer **207b** and the third gate insulating layer **206**. The second source electrode **S2** and the second drain electrode **D2** may include a conductive material including Mo, Al, Cu, Ti, or the like, and may be a single layer or a multi-layer.

(97) The first thin-film transistor TFT including the first semiconductor layer **A1** including polycrystalline silicon has high reliability, which may be used as a thin-film transistor to form a high-quality display panel.

(98) Because the second thin-film transistor TFT having the second semiconductor layer **A2** including an oxide semiconductor has high carrier mobility and low leakage current, a voltage drop may not be large even when a driving time is long. That is, because color change of an image according to a voltage drop is not large even during low-frequency driving, the low-frequency driving is possible. Because an oxide semiconductor has an advantage of having a small leakage current, leakage current may be prevented and power consumption may be reduced at the same time by using an oxide semiconductor in at least one of other thin-film transistors other than the driving thin-film transistor.

(99) The first planarization layer **209a** and the second planarization layer **209b** may be on the second interlayer insulating layer **207b**. A conductive pattern such as a line or the like may be formed between the first planarization layer **209a** and the second planarization layer **209b**, and this is beneficial for high integration.

(100) The first planarization layer **209a** may cover the pixel circuit **PC**. The second planarization layer **209b** may be on the first planarization layer **209a**. The first planarization layer **209a** and the second planarization layer **209b** may include an organic material or an inorganic material, and may be a single layer or a multi-layer. The first planarization layer **209a** and the second planarization layer **209b** may include benzocyclobutene (BCB), polyimide, HMDSO, a general commercial polymer such as PMMA or PS, a polymer derivative having a phenol group, an acrylic polymer, an imide polymer, an aryl ether polymer, an amide polymer, a fluorine polymer, a p-xylene polymer, a vinyl alcohol polymer, or the like. As another embodiment, the first planarization layer **209a** and the second planarization layer **209b** may include an inorganic insulating material such as silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al₂O₃), titanium oxide (TiO₂), tantalum oxide (Ta₂O₅), hafnium oxide (HfO₂), zinc oxide (ZnO), or the like. When forming the first planarization layer **209a** and the second planarization layer **209b**, a chemical and mechanical polishing operation may be performed to provide a flat top surface.

(101) The organic light-emitting diode OLED may be on the second planarization layer **209b**. The first electrode **221** of the organic light-emitting diode OLED may be connected to the pixel circuit **PC** through a connection electrode **CM** on the first planarization layer **209a**.

(102) The connection electrode **CM** may be between the first planarization layer **209a** and the second planarization layer **209b**. The connection electrode **CM** may include a conductive material including Mo, Al, Cu, Ti, or the like, and may be a single layer or a multi-layer. For example, the connection electrode **CM** may have a multi-layered structure of Ti/Al/Ti.

(103) FIG. **8** is a cross-sectional view of the display panel **10** taken along line VIII-VIII' of FIG. **6**.

(104) Referring to FIG. **8**, the display panel **10** includes the opening area **OA**, the display area **DA**, and the first non-display area **NDA1** between the opening area **OA** and the display area **DA**. The display panel **10** may include a first opening **10H** corresponding to the opening area **OA**.

(105) The display panel **10** is illustrated as using the pixel circuit **PC** of FIG. **7B**, but the exemplary

embodiments are not limited thereto. For example, the display panel **10** may use the pixel circuit PC of FIG. 7A.

(106) Referring to the display area DA, the first thin-film transistor TFT, the second thin-film transistor TFT_o, and the storage capacitor C_{st} on the substrate **100** may be in the display area DA.

(107) A plurality of insulating layers **201** to **209b** may be between semiconductor layers and electrodes of the first and second thin-film transistors TFT and TFT_o and between electrodes of the storage capacitor C_{st}. The organic light-emitting diode OLED electrically connected to the pixel circuit PC and the capping layer **230** may be in the display area DA. A plurality of insulating layers **211** and **213** may be around the organic light-emitting diode OLED.

(108) An encapsulation layer **300** may cover the organic light-emitting diode OLED having the first electrode **221**, the intermediate layer **222**, and the second electrode **223**. The encapsulation layer **300** may include at least one organic encapsulation layer and at least one inorganic encapsulation layer. As an embodiment, the encapsulation layer **300** may include a first inorganic encapsulation layer **310**, a second inorganic encapsulation layer **330**, and an organic encapsulation layer **320** between the first inorganic encapsulation layer **310** and the second inorganic encapsulation layer **330**. As another embodiment, the number of organic encapsulation layers, the number of the inorganic encapsulation layers, and a stacking order thereof may be changed.

(109) The first inorganic encapsulation layer **310** and the second inorganic encapsulation layer **330** may include an inorganic insulating material such as silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al₂O₃), titanium oxide (TiO₂), tantalum oxide (Ta₂O₅), hafnium oxide (HfO₂), or zinc oxide (ZnO), and may be formed by chemical vapor deposition (CVD) or the like. The organic encapsulation layer **320** may include a polymer-based material. The polymer-based material may include a silicone-based resin, an acryl-based resin, an epoxy-based resin, polyimide, polyethylene, or the like.

(110) The first non-display area NDA₁ may include a first sub-non-display area SNDA₁ relatively adjacent to the display area DA and a second sub-non-display area SNDA₂ relatively adjacent to the opening area OA or the first opening **10H**.

(111) The first sub-non-display area SNDA₁ may be an area through which signal lines, for example, a plurality of data lines DL pass, as described in FIG. 5. The plurality of data lines DL may correspond to data lines DL bypassing the opening area OA. The first sub-non-display area SNDA may be a wiring area or a bypass area through which the plurality of data lines DL pass.

(112) Referring to FIG. 8, the plurality of data lines DL may be on different layers with the second interlayer insulating layer **207b** therebetween, and may overlap each other or alternate with each other. As another embodiment, the plurality of data lines DL may be on the same insulating layer. When the plurality of data lines DL are vertically arranged with an insulating layer therebetween, the distance between the plurality of data lines DL may be reduced, and thus, the width of the first non-display area NDA₁ may be reduced. As another embodiment, a plurality of scan lines SL bypassing the opening area OA may also be located in the first sub-non-display area SNDA₁.

(113) A dam **240** may be in the second sub-non-display area SNDA₂. As an embodiment, a multi-layered dam **240** may be on the second interlayer insulating layer **207b**. For example, as shown in FIG. 8, the dam **240** may include at least one layer. When forming the organic encapsulation layer **320** of the encapsulation layer **300**, the dam **240** may control the flow of the organic encapsulation layer **320**. The dam **240** may include a first layer **241**, a second layer **242** on the first layer **241**, and a third layer **243** on the second layer **242**. The first layer **241** may be formed in the same operation as that of the second planarization layer **209b** and include the same material as that of the second planarization layer **209b**. The second layer **242** may be formed in the same operation as that of the pixel defining film **211** and include the same material as that of the pixel defining film **211**. The third layer **243** may be formed in the same operation as that of the spacer **213** and include the same material as that of the spacer **213**. When the dam **240** includes at least one of the insulating layers **201** to **213** formed on the substrate **100**, it is not limited to any one insulating layer.

(114) The first functional layer **222a**, the second functional layer **222c**, the second electrode **223** and the capping layer **230**, which extend from the display area DA, may be on the dam **240**. The emission layer **222b** may not be on the dam **240**. In other words, the intermediate layer **222** except for the emission layer **222b**, the second electrode **223** and the capping layer **230**, may be disposed on the dam **240**.

(115) The second sub-non-display area SNDA2 may include the sacrificial layer area SLA from which the organic material between the substrate **100** and the encapsulation layer **300** has been removed. The sacrificial layer area SLA may be an area between the dam **240** and the opening area OA. The sacrificial layer pattern **930** may be in the sacrificial layer area SLA. The sacrificial layer pattern **930** may be patterned during a lift-off operation of a sacrificial layer (**910** of FIG. 9A), the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** by using a laser lift off (LLO) method.

(116) The sacrificial layer pattern **930** includes a metal material. As an embodiment, the sacrificial layer pattern **930** may be formed of the same material as that of the first electrode **221** of the organic light-emitting diode OLED in the same operation as that of the first electrode **221** of the organic light-emitting diode OLED. For example, the sacrificial layer pattern **930** may have a structure in which ITO/Ag/ITO are stacked.

(117) The sacrificial layer pattern **930** may be formed in at least one area of areas around a start point Ls where irradiation of a laser beam starts and around a finish point Lf where the irradiation of a laser beam is finished, during laser processing of the sacrificial layer area SLA. The sacrificial layer pattern **930** may include a first sacrificial layer pattern **931** and a second sacrificial layer pattern **932** in the sacrificial layer area SLA.

(118) The first sacrificial layer pattern **931** may be spaced apart from the dam **240** around the start point Ls where the irradiation of a laser beam starts. At least one first sacrificial layer pattern **931** may be arranged in the sacrificial layer area SLA. The first sacrificial layer pattern **931** may have a discontinuous pattern form. For example, in the first sacrificial layer pattern **931**, a plurality of linear patterns or a plurality of curved patterns may be apart from each other. As another embodiment, the first sacrificial layer pattern **931** may be a continuous pattern form. For example, in the first sacrificial layer pattern **931**, a linear pattern or a curved pattern may extend in one direction of the sacrificial layer area SLA without disconnection.

(119) The second sacrificial layer pattern **932** may be arranged in the sacrificial layer area SLA around the finish point Lf where the irradiation of a laser beam is finished, to be apart from the opening area OA. Similar to the first sacrificial layer pattern **931**, at least one second sacrificial layer pattern **932** may be arranged in the sacrificial layer area SLA, and may have a pattern structure in which a linear pattern or a curved pattern is discontinuous. As another embodiment, at least one second sacrificial layer pattern **932** may be arranged in the sacrificial layer area SLA, and may have a structure in which a linear pattern or a curved pattern is continuous.

(120) As described above, the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932** may be respectively arranged on both edges of the sacrificial layer area SLA. The sacrificial layer pattern **930** may be arranged not only on both edges of the sacrificial layer area SLA, but also over the entire area of the sacrificial layer area SLA according to the degree of overlap of an irradiated laser beam. On the other hand, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** may not be provided in the sacrificial layer area SLA.

(121) The first inorganic encapsulation layer **310** may extend from the display area DA to the first non-display area NDA1. The first inorganic encapsulation layer **310** may cover the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932**. The second inorganic encapsulation layer **330** may cover the first inorganic encapsulation layer **310**.

(122) In the sacrificial layer area SLA, the first inorganic encapsulation layer **310** may be in contact with the second interlayer insulating layer **207b**, which is an inorganic insulating layer exposed

between the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932**. Because the first functional layer **222a**, the second functional layer **222c**, and the capping layer **230**, which are organic materials, are not exposed on a sidewall of the first opening **10H**, foreign substances such as moisture or the like may be prevented from penetrating into the organic light-emitting diode OLED through the first opening **10H**.

(123) In the first non-display area **NDA1**, the first inorganic encapsulation layer **310** may cover an outer surface of the dam **240**. The organic encapsulation layer **320** may be formed by applying and curing a monomer. The flow of the monomer may be controlled by the dam **240**. An end portion of the organic encapsulation layer **320** may be located on a side portion of the dam **240** facing the display area **DA**.

(124) The second inorganic encapsulation layer **330** may cover the dam **240**, as the first inorganic encapsulation layer **310**. A portion of the second inorganic encapsulation layer **330** may be in contact with the first inorganic encapsulation layer **310**. For example, in the second sub-non-display area **SNDA2**, a portion of the second inorganic encapsulation layer **330** may be in contact with the first inorganic encapsulation layer **310**. The first inorganic encapsulation layer **310** and the second inorganic encapsulation layer **330** may also contact each other on an upper surface of the dam **240**.

(125) FIGS. **9A** to **9E** are cross-sectional views sequentially showing an illustrative method of manufacturing the display panel **10** shown in FIG. **8**. FIGS. **10A** to **10D** are plan views of embodiments of a sacrificial layer shown in FIG. **9A** illustrating various patterns of slits in the sacrificial layer.

(126) Referring to FIG. **9A**, the pixel circuit **PC** including at least one thin-film transistor **TFT** and **TFTo** is formed in the display area **DA**. As an embodiment, the pixel circuit **PC** may include the first thin-film transistor **TFT** including a polysilicon semiconductor and a second thin-film transistor **TFTo** including an oxide semiconductor.

(127) In the display area **DA**, the first planarization layer **209a** covers the pixel circuit **PC**. The connection electrode **CM** is formed on the first planarization layer **209a**. The second planarization layer **209b** is formed on the connection electrode **CM**. The first electrode **221** connected to the connection electrode **CM** is formed on the second planarization layer **209b**.

(128) In the first non-display area **NDA1**, a first opening **209h** is formed by patterning the first planarization layer **209a**. The first layer **241** of a plurality of dams **240** is formed in the same operation as that of the second planarization layer **209b**. The first layer **241** is on the second interlayer insulating layer **207b**.

(129) The sacrificial layer **910** is formed in the first non-display area **NDA1**. The sacrificial layer **910** is formed on the second interlayer insulating layer **207b** through the first opening **209h**. The sacrificial layer **910** may have an annular structure formed along a periphery of the opening area **OA** shown in FIG. **6**.

(130) The sacrificial layer **910** may be simultaneously formed when forming an element of the pixel circuit **PC**. For example, the sacrificial layer **910** may be formed in the same operation as that of the first electrode **221** electrically connected to the pixel circuit **PC**, and may include the same material as that of the first electrode **221**. The sacrificial layer **910** may include a conductive oxide, a metal material, or a metal compound. The sacrificial layer **910** may further include a film including **ITO**, **IZO**, **ZnO**, and **In₂O₃** above and below a reflective film including a metal. For example, the sacrificial layer **910** may have a structure in which **ITO/Ag/ITO** are stacked.

(131) A plurality of slits **920** may be formed in the sacrificial layer **910**. The plurality of slits **920** may penetrate completely through the material of the sacrificial layer **910** in the thickness direction of the sacrificial layer **910** in the first non-display area **NDA1**.

(132) Referring to FIG. **10A**, a plurality of slits **1011** may be formed over substantially the entire area of a sacrificial layer **1010**. Each of the plurality of slits **1011** may have a generally rectangular pattern and may be apart from each other.

(133) Referring to FIG. 10B, a sacrificial layer **1020** may be separated into a plurality of sacrificial layer portions **1020a**. The plurality of sacrificial layer portions **1020a** may be apart from each other. The plurality of sacrificial layer portions **1020a** may have a generally rectangular pattern. A slit **1021** may be formed between the plurality of separated sacrificial layer portions **1020a**. The slit **1021** may have a linear pattern.

(134) Referring to FIG. 10C, a plurality of slits **1031** may be formed over substantially the entire area of a sacrificial layer **1030**. Each of the plurality of slits **1031** may have a shape obtained by rotating the slit **1011** of FIG. 10A by 90 degrees. Each of the plurality of slits **1031** may have a generally rectangular pattern and may be apart from each other.

(135) Referring to FIG. 10D, a sacrificial layer **1040** may be separated into a plurality of sacrificial layer portions **1040a**. The plurality of sacrificial layer portions **1040a** may have a shape obtained by rotating the sacrificial layer portion **1020a** of FIG. 10B by 90 degrees. The plurality of sacrificial layer portions **1040a** may be apart from each other. The plurality of sacrificial layer portions **1040a** may have a generally rectangular pattern. A slit **1041** may be formed between the plurality of separated sacrificial layer portions **1040a**. The slit **1041** may have a linear pattern.

(136) Referring to FIG. 9A again, the plurality of slits **920** may be formed in various patterns other than a linear pattern or a curved pattern. In addition, the plurality of slits **920** may have a pattern form in which a linear pattern or a curved pattern over substantially the entire area of the sacrificial layer **910** is discontinuous. As another embodiment, the plurality of slits **920** may have a pattern form in which a linear pattern or a curved pattern over substantially the entire area of the sacrificial layer **910** is continuous.

(137) Referring to FIG. 9B, the pixel defining film **211** is formed on the first electrode **221** in the display area DA. The pixel defining film **211** is formed to expose a portion of the first electrode **221**. The spacer **213** is formed on the pixel defining film **211**.

(138) In the first non-display area NDA1, the second layer **242** and the third layer **243** is sequentially formed on the first layer **241**. The second layer **242** is formed in the same operation as that of the pixel defining film **211**. The third layer **243** is formed in the same operation as that of the spacer **213**. As an embodiment, the dam **240** of a triple layer is formed on the second interlayer insulating layer **207b**. At least one dam **240** may be formed in the first non-display area NDA1.

(139) In the display area DA, the organic light-emitting diode OLED electrically connected to the pixel circuit PC is formed. The intermediate layer **222** including the first functional layer **222a**, the emission layer **222b**, and the second functional layer **222c** is formed on the first electrode **221**, and the second electrode **223** is formed on the intermediate layer **222**. The second electrode **223** may include a (semi)transparent layer including Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, alloys thereof, or the like. As another embodiment, the second electrode **223** may further include a layer such as ITO, IZO, ZnO, and In₂O₃ above the (semi)transparent layer including the above-stated material. As another embodiment, the second electrode **223** may include a metal material including Ag.

(140) In the first non-display area NDA1, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** are sequentially stacked on an outer surface of the dam **240** and an upper surface of the sacrificial layer **910**.

(141) The first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** are formed on substantially the entire surface of the substrate **100**. The first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** integrally extend on the outer surface of the dam **240** and on the sacrificial layer **910** having the plurality of slits **920**. The first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** cover the sacrificial layer **910**.

(142) FIGS. 11A to 11C are cross-sectional views sequentially showing an illustrative operation of removing a sacrificial layer, a functional layer, and a second electrode, which are stacked, as shown in FIG. 9B, by irradiating a laser beam. Referring to FIG. 11A, the plurality of slits **920** are formed

in the sacrificial layer **910**. The first functional layer **222a** and the second functional layer **222c** are formed on a first surface **910a** of the sacrificial layer **910** and in the plurality of slits **920**. The first functional layer **222a** and the second functional layer **222c** integrally extend. The first surface **910a** of the sacrificial layer **910** may be a surface opposite from a base **100s**. The base **100s** may correspond to an area from the substrate **100** of FIG. **8** to the second interlayer insulating layer **207b**. The second electrode **223** is formed on the first functional layer **222a** and the second functional layer **222c**. The thickness of the first functional layer **222a** and the second functional layer **222c** is much greater than the thickness of the second electrode **223**. For example, the thickness of the first functional layer **222a** and the second functional layer **222c** may be several tens of times greater than that of the second electrode **223**. The capping layer **230** is formed on the second electrode **223**.

(143) Referring to FIG. **9B** again, laser beams having different densities are irradiated to the sacrificial layer **910**, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** in two steps. When irradiating a 2-step laser beam, the sacrificial layer **910**, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** may be lifted off from the substrate **100**. In other words, two laser beams (e.g., **L1** and **L2** shown in FIGS. **11A** and **11B**) having different densities can be irradiated to the layers by using a 2-step Laser Lift Off (LLO) method.

(144) An operation in which the sacrificial layer **910**, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** are lifted off from the substrate **100** will be described in detail below, as shown in FIGS. **11A** to **11C**.

(145) First, referring to FIG. **11A**, a first laser beam **L1** may have a wavelength of infrared light. When the laser beam is infrared light because the transmittance thereof with respect to the substrate **100** and insulating layers **201** to **207b** of FIG. **8** is greater than or equal to 80% to 90%, the laser beam efficiently reaches the sacrificial layer **910**.

(146) A first laser beam **L1** proceeds in a thickness direction of the base **100s** to be irradiated toward the sacrificial layer **910**, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230**, which are stacked. The second electrode **223** is lifted off from the first functional layer **222a** and the second functional layer **222c** by the first laser beam **L1**.

(147) In detail, the first laser beam **L1** is irradiated onto a second surface **910b** of the sacrificial layer **910** facing the base **100s**. At the same time, the first laser beam **L1** passes through the plurality of slits **920** formed in the sacrificial layer **910**. At that time, the first laser beam **L1** is irradiated onto one surface of the second electrode **223** via the first functional layer **222a** and the second functional layer **222c**.

(148) The energy density of the first laser beam **L1** has less influence on the sacrificial layer **910** and has an intensity capable of lifting off the second electrode **223**. For example, the sacrificial layer **910** may have a structure in which ITO/Ag/ITO are stacked. The second electrode **223** includes a metal material including Ag. The energy density of the first laser beam **L1** for selectively lifting off the second electrode **223** may be about 0.7 J/cm² or less.

(149) Because the first laser beam **L1** is infrared light, the first functional layer **222a** and the second functional layer **222c** including an organic material are not affected, and the first laser beam **L1** may be directly irradiated onto the one surface of the second electrode **223**. The second electrode **223** absorbs the first laser beam **L1**. The second electrode **223** is thermally expanded, and the second electrode **223** is lifted off from the first functional layer **222a** and the second functional layer **222c**. The capping layer **230** on the second electrode **223** may also be lifted off together with the second electrode **223**. As such, the second electrode **223** may be removed in advance before removing the sacrificial layer **910**.

(150) Next, referring to FIG. **11B**, a second laser beam **L2** proceeds in the thickness direction of the base **100s** to be irradiated toward the sacrificial layer **910**, the first functional layer **222a**, and the

second functional layer **222c**, which are stacked. The irradiated second laser beam **L2** lifts the sacrificial layer **910** off from the base **100s**.

(151) In detail, the second laser beam **L2** is irradiated onto the second surface **910b** of the sacrificial layer **910** facing the base **100s**. The energy density of the second laser beam **L2** is relatively greater than the energy density of the first laser beam **L1** and has an intensity capable of lifting off the sacrificial layer **910**. For example, the energy density of the second laser beam **L2** may be about 1.5 J/cm² or more.

(152) When the second laser beam **L2** is irradiated to the sacrificial layer **910**, the sacrificial layer **910** absorbs the second laser beam **L2**. The sacrificial layer **910** is thermally expanded, and the second surface **910b** of the sacrificial layer **910** to which a laser beam is irradiated is lifted off from the base **100s**. As the sacrificial layer **910** is lifted off, the first functional layer **222a** and the second functional layer **222c** on the sacrificial layer **910** may be also lifted off together with the sacrificial layer **910**.

(153) Because the second electrode **223** is lifted off in advance, when the sacrificial layer **910** is thermally expanded, the sacrificial layer **910**, the first functional layer **222a**, and the second functional layer **222c** may be lifted off without disturbance of the first functional layer **222a** and the second functional layer **222c**. Accordingly, it is possible to prevent scattering of foreign substances that may occur during a LLO operation in advance.

(154) Subsequently, referring to FIG. **11C**, the sacrificial layer pattern **930** may be patterned on the base **100s**. When laser processing the sacrificial layer area **SLA** in which the sacrificial layer **910** is formed, an area to which a laser beam is not irradiated is generated around the start point **Ls** where the irradiation of a laser beam starts or around the finish point **Lf** where the irradiation of a laser beam is finished. The sacrificial layer pattern **930** may correspond to a portion of the sacrificial layer **910** remaining in the sacrificial layer area **SLA** when the sacrificial layer **910** is removed.

(155) In detail, the laser beam may be irradiated from an area adjacent to the dam **240** of FIG. **8** to the opening area **OA** while rotating in a spiral shape. Due to the characteristics of a laser operation, an area of which the sacrificial layer **910** is not processed exists around the start point **Ls** where the irradiation of a laser beam starts or around the finish point **Lf** where the irradiation of a laser beam is finished. A portion of the sacrificial layer **910** remains in the area of which the sacrificial layer **910** is not processed, so that the portion of the sacrificial layer remains as the sacrificial layer pattern **930**.

(156) The first sacrificial layer pattern **931** may be patterned around the start point **Ls** where the irradiation of a laser beam starts. The vicinity of the start point **Ls** where the irradiation of a laser beam starts may be the sacrificial layer area **SLA** adjacent to the dam **240** of FIG. **8**. The second sacrificial layer pattern **932** may be patterned around the finish point **Lf** where the irradiation of a laser beam is finished. The vicinity of the finish point **Lf** where the irradiation of a laser beam is finished may be the sacrificial layer area **SLA** adjacent to the opening area **OA** of FIG. **8**.

(157) The first sacrificial layer pattern **931** and the second sacrificial layer pattern **932** may be respectively patterned in a linear pattern or a curved pattern around the start point **Ls** where the irradiation of a laser beam starts and around the finish point **Lf** where the irradiation of a laser beam is finished. The first sacrificial layer pattern **931** and the second sacrificial layer pattern **932** may be a discontinuous pattern or a continuous pattern. Substantially, the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932** may be a portion of a sacrificial layer **1010**, **1020**, **1030** and **1040** shown in FIGS. **10A** to **10D**.

(158) Referring to FIG. **9C**, when the sacrificial layer **910** is lifted off from the substrate **100**, the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932**, which are a portion of the sacrificial layer **910**, remain in the sacrificial layer area **SLA**. On the other hand, a remaining portion of the sacrificial layer **910** except the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932**, the first functional layer **222a**, the second functional layer **222c**, the second electrode **223**, and the capping layer **230** do not exist in the sacrificial layer area **SLA**.

(159) Next, referring to FIG. 9D, the encapsulation layer **300** is formed above the substrate **100**. The first inorganic encapsulation layer **310** and the second inorganic encapsulation layer **330** are formed on substantially the entire surface of the substrate **100**. The first inorganic encapsulation layer **310** extends from the display area DA to the sacrificial layer area SLA via the dam **240**. In the sacrificial layer area SLA, the first inorganic encapsulation layer **310** covers the first sacrificial layer pattern **931** and the second sacrificial layer pattern **932** remaining on the second interlayer insulating layer **207b**, and the second interlayer insulating layer **207b**.

(160) The organic encapsulation layer **320** is formed on the first inorganic encapsulation layer **310**. An end portion of the organic encapsulation layer **320** is located on the side portion of the dam **240** facing the display area DA. The dam **240** may control the flow of the organic encapsulation layer **320**.

(161) The second inorganic encapsulation layer **330** is formed on the organic encapsulation layer **320**. As the first inorganic encapsulation layer **310**, the second inorganic encapsulation layer **330** extends from the display area DA to the sacrificial layer area SLA via the dam **240**. In the sacrificial layer area SLA, the second inorganic encapsulation layer **330** is in a direct contact with the first inorganic encapsulation layer **310**.

(162) Referring to FIG. 9E, the first opening **10H** is formed by cutting the substrate **100** and the insulating layers **201** to **330** stacked on the substrate **100** along a cutting line CL. Because the first functional layer **222a**, the second functional layer **222c**, and the capping layer **230**, which include an organic material, are not exposed on a sidewall of the first opening **10H**, moisture is prevented from penetrating into the organic light-emitting diode OLED through the first opening **10H**.

(163) In display panels constructed according to the principles and embodiments of the invention and illustrative methods of manufacturing the same, particles that may be generated during the process of removing a sacrificial layer, an intermediate layer, and a second electrode, which are stacked in a non-display area between an opening area and a display area, by a LLO method may be easily controlled to avoid generating significant accumulation of harmful particles.

(164) Although certain embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concepts are not limited to such embodiments, but rather to the broader scope of the appended claims and various obvious modifications and equivalent arrangements as would be apparent to a person of ordinary skill in the art.

Claims

1. A display panel comprising: a substrate having an opening and a display area surrounding the opening; a light-emitting element in the display area and including a first electrode, an intermediate layer, and a second electrode; a multi-layered dam in a non-display area between the opening and the display area; an encapsulation layer extending substantially over the display area and the non-display area; and a first layer pattern disposed in one area of the non-display area and having a bottom surface coplanar with a corresponding bottom surface of the multi-layered dam.
2. The display panel of claim 1, wherein the first layer pattern is disposed in at least one of the non-display area adjacent to the multi-layered dam or the non-display area adjacent to the opening.
3. The display panel of claim 1, wherein the first layer pattern is arranged in the one area of the non-display area in a discontinuous linear pattern or a discontinuous curved pattern.
4. The display panel of claim 1, wherein the first layer pattern is arranged in the one area of the non-display area in a continuous linear pattern or a continuous curved pattern.
5. The display panel of claim 1, wherein the first layer pattern comprises a sacrificial layer pattern having the same material as that of the first electrode.
6. The display panel of claim 1, wherein at least one inorganic encapsulation layer in the encapsulation layer covers the first layer pattern.

7. The display panel of claim 1, wherein the opening extends completely through the substrate.
 8. The display panel of claim 1, wherein the multi-layered dam comprises: an insulating layer on the substrate; a first organic insulating layer directly contacting the insulating layer; and a second organic insulating layer directly contacting the first organic insulating layer.
 9. The display panel of claim 8, wherein the intermediate layer overlaps the multi-layered dam and directly contacts the insulating layer, the first organic insulating layer, and the second organic insulating layer.
 10. The display panel of claim 1, wherein the intermediate layer overlaps and directly contacts the multi-layered dam.
 11. The display panel of claim 1, wherein the bottom surface of the multi-layered dam extends between and ends at first and second side surfaces of the multi-layered dam.
 12. The display panel of claim 11, wherein the bottom surface of the first layer pattern and the bottom surface of the multi-layered dam directly contact an upper surface of a second interlayer insulating layer.
 13. The display panel of claim 1, wherein the first layer pattern is spaced apart from the multi-layered dam in a horizontal direction by the intermediate layer overlapping the multi-layered dam in a thickness direction.
 14. The display panel of claim 13, wherein the first layer pattern is spaced apart from the multi-layered dam in the horizontal direction by an inorganic encapsulation layer overlapping the multi-layered dam, the first layer pattern, and the intermediate layer in a thickness direction.
 15. The display panel of claim 1, wherein the encapsulation layer directly contacts an upper surface of the first layer pattern, and the encapsulation layer is an inorganic encapsulation layer.
-