



US012406788B2

(12) **United States Patent**
Chen et al.

(10) **Patent No.: US 12,406,788 B2**

(45) **Date of Patent: Sep. 2, 2025**

(54) **M-TYPE HEXAFERRITE COMPRISING
ANTIMONY**

(71) Applicant: **ROGERS CORPORATION**, Chandler,
AZ (US)

(72) Inventors: **Yajie Chen**, Brighton, MA (US); **Qifan
Li**, Hubei (CN)

(73) Assignee: **ROGERS CORPORATION**, Chandler,
AZ (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 755 days.

(21) Appl. No.: **17/771,683**

(22) PCT Filed: **Oct. 29, 2020**

(86) PCT No.: **PCT/US2020/057827**

§ 371 (c)(1),

(2) Date: **Apr. 25, 2022**

(87) PCT Pub. No.: **WO2021/087022**

PCT Pub. Date: **May 6, 2021**

(65) **Prior Publication Data**

US 2022/0367094 A1 Nov. 17, 2022

Related U.S. Application Data

(60) Provisional application No. 62/927,783, filed on Oct.
30, 2019.

(51) **Int. Cl.**
H01F 1/34 (2006.01)
C01G 30/00 (2006.01)
C01G 51/66 (2025.01)
C08K 3/22 (2006.01)
H01F 1/36 (2006.01)
H01F 1/37 (2006.01)

(52) **U.S. Cl.**
CPC **H01F 1/348** (2013.01); **C01G 51/66**
(2013.01); **C08K 3/22** (2013.01); **C01P**
2002/54 (2013.01); **C01P 2006/42** (2013.01);
C08K 2003/2289 (2013.01); **C08K 2201/01**
(2013.01)

(58) **Field of Classification Search**
CPC . H01F 1/34; H01F 1/342; H01F 1/348; H01F
1/36; H01F 1/37; C01G 30/002; C01G
30/005; C01P 2002/52; C01P 2006/42;
C08K 2003/2282

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,020,426 A	2/1962	Van Der Burgt
3,036,007 A	5/1962	Buykx et al.
4,569,775 A	2/1986	Kubo et al.
4,664,831 A	5/1987	Hibst et al.
4,957,812 A	9/1990	Aoki et al.
5,110,651 A	5/1992	Massard et al.
5,452,167 A	9/1995	Nago
5,494,749 A	2/1996	Kubo et al.
5,591,276 A	1/1997	Yoshizawa et al.
5,593,612 A	1/1997	Lubitz
5,616,414 A *	4/1997	Hopstock G11B 5/70678 252/62.62
6,071,430 A	6/2000	Lebourgeois et al.
6,358,432 B1	3/2002	Tomono et al.
6,436,307 B1	8/2002	Lebourgeois et al.
6,736,990 B2	5/2004	Aoki et al.
7,348,374 B2	3/2008	Martinazzo
7,482,977 B2	1/2009	Kuroda et al.
8,263,224 B2	9/2012	Tokiwa
8,305,281 B2	11/2012	Suetsuna et al.
8,758,721 B2	6/2014	Hill
9,596,755 B2	3/2017	Sethumadhavan et al.
10,071,421 B2	9/2018	Suetsuna et al.
10,090,088 B2	10/2018	Suetsuna et al.
10,468,169 B2	11/2019	Chen et al.
2002/0050309 A1	5/2002	Marusawa
2003/0052298 A1	3/2003	Wang et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN	101723654 A	6/2010
CN	102486655 A	6/2012

(Continued)

OTHER PUBLICATIONS

International Search Report; International Application No. PCT/
US2020/057827; International Filing Date: Oct. 29, 2020; Date of
Mailing: Feb. 19, 2021; 6 pages.

(Continued)

Primary Examiner — Matthew E. Hoban

Assistant Examiner — Lynne Edmondson

(74) *Attorney, Agent, or Firm* — CANTOR COLBURN
LLP

(57) **ABSTRACT**

In an aspect, a ferrite composition can comprise a SbCo—
M-type ferrite having the formula: $Me_{1-x}Sb_xCo_{y+x}M'_y$
 $Fe_{12-x-2y}O_{19}$, wherein Me is at least one of Sr, Pb, or Ba; M' is
at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is
0.8 to 1.3. In another aspect, a method of making the ferrite
composition comprises mixing ferrite precursor compounds
comprising Me, Fe, Sb, Co, and M'; and sintering the ferrite
precursor compounds in an oxygen atmosphere to form the
SbCo—M-type ferrite. In yet another aspect, a composite
comprises the ferrite composition and a polymer. In still
another aspect, an article comprises the ferrite composition.

(56)

References Cited**U.S. PATENT DOCUMENTS**

2003/0091841	A1	5/2003	Marusawa
2004/0054029	A1	3/2004	Fujiki et al.
2007/0231614	A1	10/2007	Kondo et al.
2009/0057606	A1	3/2009	Tada et al.
2009/0101873	A1	4/2009	Tan et al.
2009/0266604	A1	10/2009	Tokiwa
2009/0297432	A1	12/2009	Hill
2010/0060539	A1	3/2010	Suetsuna et al.
2010/0068512	A1	3/2010	Imaoka et al.
2011/0147643	A1	6/2011	Ryou et al.
2012/0049100	A1	3/2012	Yonetsu et al.
2012/0068103	A1	3/2012	Hill et al.
2012/0085963	A1	4/2012	An et al.
2012/0229354	A1	9/2012	Ishikura et al.
2013/0115160	A1	5/2013	Hill et al.
2013/0292602	A1	11/2013	Hill
2013/0342414	A1	12/2013	Hong et al.
2014/0264145	A1	9/2014	Ray et al.
2014/0291571	A1	10/2014	Riden
2014/0346387	A1	11/2014	Hill et al.
2015/0310971	A1	10/2015	Kmetz et al.
2016/0086700	A1	3/2016	Suetsuna et al.
2016/0086728	A1	3/2016	Suetsuna et al.
2016/0099498	A1	4/2016	Pance et al.
2016/0113113	A1	4/2016	Sethumadhavan et al.
2016/0118171	A1	4/2016	Hill
2016/0276072	A1	9/2016	Sethumadhavan et al.
2017/0098885	A1	4/2017	Hill et al.
2017/0213628	A1	7/2017	Chen et al.
2018/0016157	A1	1/2018	Chen et al.
2019/0013128	A1	1/2019	Chen et al.
2019/0040226	A1	2/2019	Aga et al.
2019/0081377	A1	3/2019	Hill et al.
2019/0264005	A1	8/2019	Horn et al.
2019/0300379	A1	10/2019	Kojima et al.
2019/0318858	A1	10/2019	Chen et al.
2021/0032121	A1	2/2021	Li et al.
2021/0043346	A1	2/2021	Li et al.
2021/0065943	A1	3/2021	Zhang et al.
2021/0179442	A1	6/2021	Chen et al.
2021/0225566	A1	7/2021	Zhang et al.
2021/0246046	A1	8/2021	Chen et al.
2021/0261433	A1	8/2021	Chen et al.
2022/0367093	A1	11/2022	Chen et al.
2023/0352221	A1	11/2023	Chen et al.
2023/0352222	A1	11/2023	Chen et al.
2023/0352223	A1	11/2023	Chen et al.
2023/0399237	A1	12/2023	Chen et al.
2024/0158302	A1	5/2024	Chen et al.
2024/0203624	A1	6/2024	Chen et al.

FOREIGN PATENT DOCUMENTS

CN	103304186	A	9/2013
CN	104193224	A	12/2014
CN	104379537	A	2/2015
DE	3907220		9/1990
EP	0620571	A2	10/1994
EP	0884740	A1	12/1998
EP	0905718	A1	3/1999
EP	1541641	A1	6/2005
EP	1652829	A2	5/2006
EP	2028663	A1	2/2009
EP	2214180	A1	8/2010
EP	2784044	A1	10/2014
EP	3012843	A1	4/2016
GB	1105788	A	3/1968
JP	S621149	A	1/1987
JP	S6245005	A	2/1987
JP	62216922	A	9/1987
JP	S62216922	A	9/1987
JP	S6489504	A	4/1989
JP	H01200605	A	8/1989
JP	H05101930	A	4/1993
JP	H0615411	B2	3/1994

JP	H06338410	A	12/1994
JP	H09167703		6/1997
JP	H09213513	A	8/1997
JP	H09232123	A	9/1997
JP	2000235916	A	8/2000
JP	2000277973		10/2000
JP	2001085210	A	3/2001
JP	2009105365	A	5/2009
JP	2009155545	A	7/2009
JP	2017037999	A	2/2017
JP	6534418	B2	6/2019
TW	201628263		8/2016
WO	9600454	A1	1/1996
WO	2011081399	A2	7/2011
WO	2012103020	A2	8/2012
WO	2016064459		4/2016
WO	2016123598	A1	8/2016
WO	2017068444		4/2017
WO	2018043943	A1	3/2018
WO	2020162295	A1	8/2020
WO	2021061599	A1	4/2021
WO	2021162886	A1	8/2021

OTHER PUBLICATIONS

Pullar, "Hexagonal Ferrites: A Review of the synthesis, properties and application of hexaferrite ceramics," Mar. 2012, Progress in Material Science, vol. 57, No. 7, pp. 1191-1334.

Written Opinion; International Application No. PCT/US2020/057827; International Filing Date: Oct. 29, 2020; Date of Mailing: Feb. 19, 2021; 10 pages.

Allia et al.; "Fe304 nanoparticles and nanocomposites and potential application in biomedicine and in communication technologies: Nanoparticle aggregation, interaction, and effective magnetic anisotropy"; J. of Applied Physics 116; 113903 (2014) 10 pgs.

Aoyama et al.; "Preparation and Characterization of Z-type Hexaferrites, Ba3(1-x)Sr3xCo2Fe24O41 with x=0-0.5, via a two-step calcination with an intermediate wet milling"; J.Electroceram; 17; pp. 61-64 (2006).

Bid et al.; "Microstructure Characterization of Mechano-synthesized Nanocrystalline NiFe2O4 by Rietveld's Analysis"; Physica E 39; pp. 175-184; (2007).

Bierlich et al.; "Low-temperature sintering and magnetic properties of Sc- and In-substituted M-type hexagonal barium ferrites for microwave applications"; Abstract, Feb. 2017 Materials Research Bulletin 86:19-23 ;11 pages.

Boix, Rafael R., et al., "Characteristics of Aperture Coupled Microstrip Antennas on Magnetized Ferrite Substrates", IEEE Transactions on Antennas and Propagation, vol. 53, No. 6, (Jun. 1, 2005), pp. 1957-1966.

Brando et al., "Microwave Electromagnetic Characteristics of New Substituted M-Hexaferrites BaFe12-2xAxMexO19 (A = Ru, Ir ; Me = Co, Zn)", Journal De Physique IV France, Mar. 1997.

Brockman et al., Nickel-Zinc Ferrites: I, Effect of Composition on the Magnetic Properties of a Nickel-Zinc-(Cobalt) Ferrite, Sep. 1970, Journal of the American Ceramic Society, vol. 53, No. 9, pp. 518-520.

Cao et al. "Hydrogen-Induced Lateral Growth of Nickel Coating on Ba3Co2Fe24O4" (Co2Z-Based Hexaferrite during the Electroplating of Multilayer Chip Inductors," Journal of The Electrochemical Society, 2002, vol. 149 Issue 12, pp. J89-J92.

Chicinas, I.; "Soft Magnetic Nanocrystalline Powders Produced by Mechanical Alloying Routes"; Journal of Optoelectronics and Advanced Materials; 8(2); pp. 439-448; (2006).

Cruz-Montoya et al., "Synthesis and characterization of polymer nanocomposites containing magnetic nanoparticles"; Journal of Applied Physics 107; 09B506 (2010); 4 pgs.

Dedi et al., "Magnetic properties of cobalt ferrite synthesized by mechanical alloying", AIP Conference Proceedings, 1964; 020003 2018; 5 pages.

Deng, et al; Effect of Bi and Mo Doping on Magnetic and Sintered Characteristics of MgCuZn Ferrite, Journal of Inorganic Materials, 2008, pp. 670-672, vol. 23 No. 4.

(56)

References Cited

OTHER PUBLICATIONS

- EP Supplemental Search Report; EP Application No. 15853114; Mailed Nov. 21, 2017; 8 pages.
- Guo et al. Abstract of "Magnetic Properties of Ir⁴⁺ Doped Co₂Z Type Hexagonal Ferrites," Journal of Rare Earths, pp. 220-222, vol. 25, Supplement 2, Jun. 2007; 7 pgs.
- Haijun et al., "The preparation and microwave properties of Ba₃ZnCo₂-zFe₂O₄ ferrite by citrate sol-gel process", Materials Science and Engineering, B84, 2001, pp. 252-257.
- Han et al.; "Microwave-absorption properties of Fe(Mn)/ferrite nanocapsules"; J. Phys. D: Appl. Phys. 42; (2009) 5 pages.
- Hansen et al., "Antennas with Magneto-Dielectrics", Microwave and Optical Technology Letters, vol. 26, No. 2, Jul. 2000, pp. 75-78.
- Huang et al.; "Magnetic epoxy nanocomposites with superparamagnetic MnFe₂O₄ nanoparticles"; AIP Advance 5; 097183 (2015); 16 pgs.
- Ismail et al.; "Magnetic Properties of Mechanically Alloyed Cobalt-Zinc Ferrite Nanoparticles"; J. Supercond Nov Magn; 27; pp. 1293-1298; (2014).
- Kim et al., "Effects of in³⁺ site occupancy on the magnetic properties of M-type strontium hexaferrites", AIB Advances 10, 015040 (2020); <https://doi.org/10.1063/1.5130073>; 5 pages.
- Koch, C. C.; "Materials Synthesis by Mechanical Alloying"; Annu. Rev. MaterSci. 19; pp. 121-143; (1989).
- Koch, C.C.; "Intermetallic Matrix Composites Prepared by Mechanical Alloying—a Review"; Materials Science and Engineering; A244; pp. 39-48; (1998).
- Kong et al., "Ni-Zn Ferrites Composites With Almost Equal Values of Permeability and Permittivity for Low-Frequency Antenna Design," IEEE Transactions On Magnetism, Jan. 2007, pp. 6-9, vol. 43, No. 1.
- Kristiantoro et al., "Magnetic properties of cobalt ferrite synthesized by mechanical alloying", from AIP Conf 1964, 020003 (2018) Published Online May 15, 2018; 5 pages.
- Lee et al. "Figure of merit of X-type hexaferrite (Ba₂Co₂Fe₂₈O₄₆) for mobile antenna applications", Microwave and Optical Technology Letters, vol. 60, Issue 3, Feb. 5, 2018, <https://doi.org/10.1002/mop.31053>.
- Lee et al., "Low Loss Co₂Z (Ba₃Co₂Fe₂₄O₄₁)—Glass Composite for Gigahertz Antenna Application," Journal of Applied Physics, 2011, vol. 109, 07E530-2.
- Lee, Jaemin et al., "Role of Small Permeability in Gigahertz Ferrite Antenna Performance", IEEE Magnetism Letters, vol. 4, 201633; 1 page.
- Li et al. "High-frequency magnetic properties of W-type barium-ferrite BaZn₂-xCoxFe₁₆O₂₇ composites", Journal of Applied Physics 94, 5918 (2003); <https://doi.org/10.1063/1.1618945>.
- Li et al., "High-Frequency Properties and Attenuation Characteristics of WBa Hexaferrite Composites with Doping of Various Oxides," Transactions of Magnetism, Feb. 2009, pp. 670-677, vol. 45 No. 2.
- Li et al.; "Microstructure effects on shock-induced surface jetting"; Journal of Applied Physics 115: 073504 (2014); pp. 11.
- Li et al; "Static and Dynamic Magnetic Properties of Co₂Z Barium Ferrite Nanoparticle Composites"; Journal of Materials Science, 40, pp. 719-723 (2005).
- Liu et al.; "Corrigendum: Electromagnetic-wave-absorption properties of wire-like structures self-assembled by FeCo nanocapsules"; J. Phys. D: Appl. Phys. 45; (2012); 7 pages.
- Martin et al.; "Flexible Magnetic Composites"; Passive RF Component Technology, Materials Techniques and Applications; Chapter 8; 2012; pp. 156-185.
- Mattei et al., "Magnetic and dielectric properties in the UHF frequency band of half-dense Ni—Zn—Co ferrites ceramics with Fe-excess and Fe-deficiency", Journal of Magnetism and Magnetic Materials, Sep. 2017, 8 pages.
- Morch et al. "Structure and Magnetic properties of W-type hexaferrites," 2019, IUCRJ, pp. 492-499, vol. 6.
- Mou, Fangzhi et al., "Oriented Contraction: A Facile Nonequilibrium Heat-Treatment Approach for Fabrication of Maghemite Fiber-in-Tube and Tube-in-Tube Nanostructures", Langmuir 2010, 26 (19), pp. 15580-15585.
- Mu et al., "Improvement of high-frequency characteristics of Z-type hexaferrite by dysprosium doping", Journal of Applied Physics, 109, 123925, 2011, 6 pages.
- Narayanasamy et al. "Influence of mechanical milling and thermal annealing on electrical and magnetic properties of nanostructured Ni—Zn and cobalt ferrites", Bulletin of Materials Science, vol. 31, No. 3 Jun. 1, 2008; pp. 373-380.
- Ohnuma et al., "Soft Magnetic Multilayers for Micromagnetic Devices," Journal of Magnetism and Magnetic Materials, 1993, pp. 556-562, vol. 126.
- Pal et al.; "Synthesis and magnetic properties of gold coated iron oxide nanoparticles"; Journal of Applied Physics 105; 07B504 (2009); 4 pgs.
- Park et al. "Design of Wide bandwidth microwave absorber with Ferrite composites of broad magnetic loss spectrum," Advanced Materials Engineering, 2015.
- Pasko et al. "Magnetic and Structural characterization of nanosized BaCo_xZn_{2-x}Fe₁₆O₂₇ hexaferrite in the vicinity of spin reorientation transition," 2011, Journal of Physics: Conference Series 303.
- Pullar et al; "Hexagonal Ferrites: A Review of the Synthesis, Properties and Applications of Hexaferrite Ceramics"; Progress in Materials Science; 57; pp. 1191-1134; (2012).
- Sahoo et al. Enhanced Magnetolectricity in Bismuth Substituted SrFe₁₂O₁₉ Hexaferrite, Aug. 2019, Journal of Applied Physics, vol. 126, No. 7.
- Sahu et al.; "Influence of excess Fe accumulation over the surface of FePt nanoparticles: Structural and magnetic properties"; Journal of Applied Physics 113; 134303 (2013); 1 pg Abstract only.
- Sepelak et al.; "Nanocrystalline Nickel Ferrite, NiFe₂O₄: Mechanosynthesis, Nonequilibrium Cation Distribution, Canted Spin Arrangement, and Magnetic Behavior"; J.Phys.Chem. C; 111; pp. 5026-5033; (2007).
- Sepelak et al.; "Structural and Magnetic Properties of Nanosize Mechanosynthesized Nickel Ferrite"; Journal of Magnetism and Magnetic Materials; 272-276; pp. 1616-1618; (2004).
- Sharma et al.; "Ultra Low Loss Soft Magnetic Nanoparticles for Applications Up to S-band," Applied Physics Letters, vol. 103, 112402, Sep. 2013.
- Singh et al. "Static Magnetic Properties of Co and Ru substituted Ba-Sr ferrite," 2008, Materials Research Bulletin, pp. 176-184, vol. 43.
- Su et al., "Low Loss Factor Co₂Z Ferrite Composites with Equivalent Permittivity and Permeability for Ultra-high Frequency Applications," Applied Physics Letters, Aug. 2014, vol. 105 No. 062402.
- Thakur et al., "Low-loss Spinel Nanoferrite with Matching Permeability and Permittivity in the Ultrahigh Frequency Range," Journal of Applied Physics · Jul. 2010, vol. 108.
- Thanh Ba Do; "High Temperature Composite Materials and Magnetodielectric Composites for Microwave Application"; Dissertation; University of Michigan; 2010; 223 pages.
- Waje et al.; "Sintering Temperature dependence of Room Temperature Magnetic and Dielectric Properties of Co_{0.5}Zn_{0.5}Fe₂O₄ Prepared using Mechanically Alloyed Nanoparticles"; Journal of magnetism and Magnetic Materials; 322; pp. 686-691; (2010).
- Wu et al.; "Studies of high-frequency magnetic permeability of rod-shaped CrO₂ nanoparticles"; Phys. Stat. Sol. (a) 204; No. 3; pp. 755-762; 2007.
- Xu et al., "Structural, dielectric and magnetic properties of Nd-doped Co₂Z-type hexaferrites", Journal of Alloys and Compounds, 509, 2011, pp. 4290-4294.
- Yang, Guo-Min, et al., "Miniaturized Patch Antennas with Ferrite/Dielectric/Ferrite Magnetodielectric Sandwich Substrate", Piers Online, vol. 7, No. 7, (Jan. 1, 2011), pp. 609-612.
- Yang, Guo-Min, et al., "Novel Compact and Low-Loss Phase Shifters With Magnetodielectric Disturber", IEEE Microwave and Wireless Components Letters, vol. 21, No. 5, (May 1, 2011); pp. 240-242.
- Zaher et al., "Osmotically driven drug delivery through remote-controlled magnetic nanocomposite membranes"; Biomicrofluidics 9; 054113 (2015); 17 pgs.
- Zhen et al.; "Microwave absorption properties of FeNi₃ submicrometre spheres and SiO₂@FeNi₃ core-shell structures"; J. Phys. D: Appl. Phys. 43; (2010); 7 pages.

(56)

References Cited

OTHER PUBLICATIONS

Carvalheiras et al. "Synthesis of red mud derived M-type barium hexaferrites with tuneable coercivity", *Ceramics International*, vol. 46, No. 5, Nov. 7, 2019, pp. 5757-5764, XP086001988.


Li, Qifan. Development of Magnetodielectric Materials with Low Loss and High Snoek's Product for Microwave Applications, Ph.D. Dissertation to The Department of Electrical and Computer Engineering, Northeastern Univ., Boston, MA, Dec. 2020, 150 pgs.

You, Jae-Hyoung, et al. Magnetic Properties of Zn-substituted Y-type hexaferrites, Ba₂ZnFe₂-xFe₁₂O₂₂, *Journal of Magnetism and Magnetic Materials*, 471 (2019) 255-261.

Faouri et al., "High quality factor cold sintered Li₂MoO₄-BaFe₁₂O₁₉ composites for microwave applications," Mar. 2019, *Acta Materialia*, vol. 166, pp. 202-207.

Li, Qifan, et al. "Emerging magnetodielectric materials for 5G communications: 18H hexaferrites," *Acta Materialia* 231 (2022) 117854 Elsevier Ltd., 10 pages.

* cited by examiner



1

**M-TYPE HEXAFERRITE COMPRISING
ANTIMONY****CROSS REFERENCE TO RELATED
APPLICATIONS**

This application is a National Stage application of PCT/US2020/057827, filed Oct. 29, 2020, which claims the benefit of U.S. Provisional Application No. 62/927,783, filed Oct. 30, 2019, both of which are incorporated by reference in their entirety herein.

BACKGROUND

Improved performance and miniaturization are needed to meet the ever-increasing demands of devices used in very high frequency (VHF) applications, which are of particular interest in a variety of commercial and defense related industries. As an important component in radar and modern wireless communication systems, antenna elements with compact sizes are constantly being developed. It has been challenging however to develop ferrite materials for use in such high frequency applications as most ferrite materials exhibit relatively high magnetic loss at high frequencies. In general, hexagonal ferrites, or hexaferrites, are a type of iron-oxide ceramic compound that has a hexagonal crystal structure and exhibits magnetic properties. Several types of families of hexaferrites are known, including Z-type ferrites, $\text{Ba}_3\text{Me}_2\text{Fe}_{24}\text{O}_{41}$, and Y-type ferrites, $\text{Ba}_2\text{Me}_2\text{Fe}_{12}\text{O}_{22}$, where Me can be a small 2+ cation such as Co, Ni, or Zn, and Sr can be substituted for Ba. Other hexaferrite types include M-type ferrites ($(\text{Ba},\text{Sr})\text{Fe}_{12}\text{O}_{19}$), W-type ferrites ($(\text{Ba},\text{Sr})\text{Me}_2\text{Fe}_{16}\text{O}_{27}$), X-type ferrites ($(\text{Ba},\text{Sr})_2\text{Me}_2\text{Fe}_{28}\text{O}_{46}$), and U-type ferrites ($(\text{Ba},\text{Sr})_4\text{Me}_2\text{Fe}_{36}\text{O}_{60}$).

Despite improvements in ferrite composites, their use in high frequency and microwave devices is limited as these substitutions also result in an increase in the magnetic loss. Improved ferrite compositions are therefore desired.

BRIEF SUMMARY

Disclosed herein is a SbCo—M-type phase ferrite.

In an aspect, a ferrite composition comprises a SbCo—M-type ferrite having the formula: $\text{Me}_{1-x}\text{Sb}_x\text{Co}_{y+x}\text{M}'_y\text{Fe}_{12-x-2y}\text{O}_{19}$, wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3.

In another aspect, a method of making the ferrite composition comprises mixing ferrite precursor compounds comprising Me, Fe, Sb, Co, and M'; and sintering the ferrite precursor compounds in an oxygen atmosphere to form the SbCo—M-type ferrite.

In yet another aspect, a composite comprises the ferrite composition and a polymer.

In still another aspect, an article comprises the ferrite composition.

The above described and other features are exemplified by the following FIGURE, detailed description, and claims.

BRIEF DESCRIPTION OF THE DRAWING

The following FIGURE is an exemplary embodiment that is provided to illustrate the present disclosure. The FIGURE is illustrative of the example, which is not intended to limit devices made in accordance with the disclosure to the materials, conditions, or process parameters set forth herein.

2

FIG. 1 is a graphical illustration of the permeability and magnetic loss tangent with frequency for Example 1 and Example 2.


DETAILED DESCRIPTION

It was discovered that substituting at least a portion of the metal ion in an M-type hexaferrite with antimony could result in a SbCo—M-type ferrite with improved properties. Specifically, the SbCo—M-type ferrite that can have the general formula:




wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3. In the formula, x can be 0.005 to 0.1. In the formula, y can be 1 to 1.2. In the formula, Me can include Ba. In the formula, M' can include Ti.

The SbCo—M-type ferrite that can have the formula:



wherein a portion, but not all of the Ba can be substituted with at least one of Sr or Pb; wherein a portion, but not all of the Ti can be substituted with at least one of Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3. In the formula, x can be 0.005 to 0.1. In the formula, y can be 1 to 1.2.

The SbCo—M-type ferrite that can have the formula:



wherein x is 0.001 to 0.3, or 0.005 to 0.1; and y is 0.8 to 1.3, or 1 to 1.2.

The SbCo—M-type ferrite can have a planar easy magnetization (c-plane). The SbCo—M-type ferrite can have at least one of a high permeability, high operating frequency, or a low magnetic loss, making it suitable for use as an antenna or an inductor at VHF (very high frequencies), for example, of 1 to 300 megahertz, or 30 to 300 megahertz. The SbCo—M-type ferrite can have a permeability of greater than or equal to 30, or greater than or equal to 50, or 28 to 55, or 28 to 35 at a frequency of 1 to 300 megahertz in the form of a solid ceramic. The SbCo—M-type ferrite can have a magnetic loss tangent $\tan \delta$ of less than or equal to 0.3, less than or equal to 0.1, or 0.01 to 0.3 at a frequency of 1 to 300 megahertz in the form of a solid ceramic. The SbCo—M-type ferrite can have a resonant frequency of greater than or equal to 250, or 250 to 500 megahertz in the form of a solid ceramic. The SbCo—M-type ferrite can have a Snoek product (the permeability measured at a frequency of 0.01 gigahertz times the resonant frequency) of greater than or equal to 8 gigahertz, or greater than or equal to 9 gigahertz, or 9 to 15 gigahertz in the form of a solid ceramic. The SbCo—M-type ferrite can have a complex permeability at 200 megahertz of 30 to 40, or 30 to 35. The SbCo—M-type ferrite can have a complex permeability at 300 megahertz of 20 to 35, or 35 to 30.

As used herein, the magnetic complex permeability is measured using an E4991B Impedance Analyzer commercially available from Keysight Technologies (1 MHz to 1 GHz) with the 16454A test fixture. The applicable ferrite materials are toroidal cores with the dimensions: outer diameter of 16 millimeters, inner diameter of 9 millimeters, height of 3 millimeters.

The SbCo—M-type ferrite can be prepared using any suitable method. Generally, the SbCo—M-type ferrite can be formed by first forming a mixture comprising the precursor compounds including oxides of at least Me, Sb, Co, M', and Fe. For example, the mixture can comprise at least

3

MeCO_3 , Sb_2O_3 , Co_3O_4 , $\text{M}'\text{O}_2$, and Fe_2O_3 . The mixture can comprise 5 to 20 weight percent of MeCO_3 based on the total weight of the precursor compounds. The mixture can comprise 0.01 to 20 weight percent, or 5 to 20 weight percent of Sb_2O_3 based on the total weight of the precursor compounds. The mixture can comprise 1 to 15 weight percent of Co_3O_4 based on the total weight of the precursor compounds. The mixture can comprise 0.1 to 10 weight percent of $\text{M}'\text{O}_2$ based on the total weight of the precursor compounds. The mixture can comprise 50 to 80 weight percent of Fe_2O_3 based on the total weight of the precursor compounds. The mixture can further comprise an oxide of at least one of Zn, Mg, Ti, Zr, Sn, or Cu.

The mixture can be calcined in air to form a calcined ferrite comprising an M-type ferrite. The calcining can occur at a calcination temperature of 800 to 1,300 degrees Celsius ($^{\circ}\text{C}.$). The calcining can occur for a calcination time of 0.5 to 20 hours, 1 to 10 hours, or 2 to 5 hours. It is noted that the calcination step is optional and the only heating step can be the sintering.

The calcined ferrite can be crushed and optionally sieved to form particulates. The sieving can comprise sieving through a number 10 to 300 mesh screen. Coarse particles can be further ground to reduce the particle size. The particulates can have a median D50 particle size by volume of 0.5 to 50 micrometers, or 0.5 to 10 micrometers. The particle size can be determined using Horiba LA-910 laser light scattering PSD analyzer or as determined in accordance with ASTM D4464-15. The calcined ferrite can be mixed with a binder. The binder can comprise at least one of poly(vinyl alcohol), poly(vinyl butyral), methyl cellulose, poly(ethylene glycol), or poly(alkylene carbonate). The binder can be present in an amount of 8 to 12 weight percent based on the total amount of the calcined ferrite plus the binder. The binder can facilitate shaping of the calcined ferrite and can fully burn off during sintering. The bound calcined ferrite can have a median D50 particle size by volume of 10 to 300 micrometers, or 50 to 300 micrometers.

The calcined ferrite can be optionally shaped and sintered to form the SbCo—M-type ferrite. The method of shaping is not limited and can comprise at least one of uniaxial compression, isostatic pressing, casting, pressing, or the like. The pressing can occur at a pressure of 0.5 to 2 metric tons per centimeter squared. The sintering can occur at a sintering temperature of 1,000 to 1,300 $^{\circ}\text{C}.$, or 1,200 to 1,250 $^{\circ}\text{C}.$ The ramping temperature up to and down from the sintering temperature can each independently occur at a ramp rate of 1 to 5 $^{\circ}\text{C}.$ per minute. The sintering can occur for a sintering time of 1 to 20 hours, or 5 to 12 hours. The sintering can be performed in an oxygen environment to help reduce the dielectric loss. Oxygen can be introduced to the sintering chamber at a flow rate of 0.1 to 10 liters per minute. The sintered SbCo—M-type ferrite can be finished in any desired manner, for example, by cutting or polishing, depending on the application.

Prior to the sintering, an amount of bismuth oxide can be added to the calcined ferrite. The bismuth oxide can be added in an amount of 0.01 to 5 weight percent based on the total weight of the calcined ferrite. Bi_2O_3 can be added into a starting mixture or to the calcined ferrite powder, depending upon the desired distribution of Bi ions. Bi ions can be located in the crystalline lattice or can be at the grain boundaries. The addition of an additional amount of Bi_2O_3 , which can be present at grain boundaries of the M-type ferrite phase, can aid in achieving a composition that has

4

equal or substantially equal values of permeability and permittivity while retaining low magnetic and dielectric loss tangents.

The SbCo—M-type ferrite can have an average grain size of 1 to 100 micrometers, or 5 to 50 micrometers. The average grain size can be measured using conventional methods, for example, by transmission electron microscopy or field emission scanning electron microscopy.

The SbCo—M-type ferrite can be a bulk ceramic or can be present in a composite, for example, comprising the SbCo—M-type ferrite and a polymer. The polymer can comprise a thermoplastic or a thermoset. As used herein, the term “thermoplastic” refers to a material that is plastic or deformable, melts to a liquid when heated, and freezes to a brittle, glassy state when cooled sufficiently. Examples of thermoplastic polymers that can be used include cyclic olefin polymers (including polynorbornenes and copolymers containing norbornenyl units, for example, copolymers of a cyclic polymer such as norbornene and an acyclic olefin such as ethylene or propylene), fluoropolymers (for example, polyvinyl fluoride (PVF), polyvinylidene fluoride (PVDF), fluorinated ethylene-propylene (FEP), polytetrafluoroethylene (PTFE), poly(ethylene-tetrafluoroethylene (PETFE), or perfluoroalkoxy (PFA)), polyacetals (for example, polyoxyethylene and polyoxymethylene), poly(C_{1-6} alkyl)acrylates, polyacrylamides (including unsubstituted and mono-N— or di-N—(C_{1-8} alkyl)acrylamides), polyacrylonitriles, polyamides (for example, aliphatic polyamides, polyphthalamides, or polyaramides), polyamideimides, polyanhydrides, polyarylene ethers (for example, polyphenylene ethers), polyarylene ether ketones (for example, polyether ether ketones (PEEK) and polyether ketone ketones (PEKK)), polyarylene ketones, polyarylene sulfides (for example, polyphenylene sulfides (PPS)), polyarylene sulfones (for example, polyethersulfones (PES), polyphenylene sulfones (PPS), and the like), polybenzothiazoles, polybenzoxazoles, polybenzimidazoles, polycarbonates (including homopolycarbonates or polycarbonate copolymers such as polycarbonate-siloxanes, polycarbonate-esters, or polycarbonate-ester-siloxanes), polyesters (for example, polyethylene terephthalates, polybutylene terephthalates, polyarylates, or polyester copolymers such as polyester-ethers), polyetherimides (for example, copolymers such as polyetherimide-siloxane copolymers), polyimides (for example, copolymers such as polyimide-siloxane copolymers), poly(C_{1-6} alkyl)methacrylates, polyalkylacrylamides (for example, unsubstituted and mono-N— or di-N—(C_{1-8} alkyl)acrylamides), polyolefins (for example, polyethylenes, such as high density polyethylene (HDPE), low density polyethylene (LDPE), and linear low density polyethylene (LLDPE), polypropylenes, and their halogenated derivatives (such as polytetrafluoroethylenes), and their copolymers, for example, ethylene-alpha-olefin copolymers), polyoxadiazoles, polyoxymethylenes, polyphthalides, polysilazanes, polysiloxanes (silicones), polystyrenes (for example, copolymers such as acrylonitrile-butadiene-styrene (ABS) or methyl methacrylate-butadiene-styrene (MBS)), polysulfides, polysulfonamides, polysulfonates, polysulfones, polythioesters, polytriazines, polyureas, polyurethanes, vinyl polymers (for example, polyvinyl alcohols, polyvinyl esters, polyvinyl ethers, polyvinyl halides (for example, polyvinyl chloride), polyvinyl ketones, polyvinyl nitriles, or polyvinyl thioethers), a paraffin wax, or the like. A combination comprising at least one of the foregoing thermoplastic polymers can be used.

Thermoset polymers are derived from thermosetting monomers or prepolymers (resins) that can irreversibly

harden and become insoluble with polymerization or cure, which can be induced by heat or exposure to radiation (e.g., ultraviolet light, visible light, infrared light, or electron beam (e-beam) radiation). Thermoset polymers include alkyls, bismaleimide polymers, bismaleimide triazine polymers, cyanate ester polymers, benzocyclobutene polymers, benzoxazine polymers, diallyl phthalate polymers, epoxies, hydroxymethylfuran polymers, melamine-formaldehyde polymers, phenolics (including phenol-formaldehyde polymers such as novolacs and resoles), benzoxazines, polydienes such as polybutadienes (including homopolymers and copolymers thereof, e.g. poly(butadiene-isoprene)), polyisocyanates, polyureas, polyurethanes, triallyl cyanurate polymers, triallyl isocyanurate polymers, certain silicones, and polymerizable prepolymers (e.g., prepolymers having ethylenic unsaturation, such as unsaturated polyesters or polyimides), or the like. The prepolymers can be polymerized, copolymerized, or crosslinked, e.g., with a reactive monomer such as styrene, alpha-methylstyrene, vinyltoluene, chlorostyrene, acrylic acid, (meth)acrylic acid, a (C₁₋₆ alkyl)acrylate, a (C₁₋₆ alkyl) methacrylate, acrylonitrile, vinyl acetate, allyl acetate, triallyl cyanurate, triallyl isocyanurate, or acrylamide.

The SbCo—M-type ferrite can be mixed with a polymer to form the composite. The mixing can comprise mixing at a temperature of a melting point of the polymer. The mixing can comprise mixing a polymer precursor with the BiRu—Co₂M ferrite and reacting the polymer precursor to form the polymer. Methods of forming the composite are not limited and can comprise injection molding, reaction injection molding, laminating, extruding, compression molding, calendering, casting, and the like. The composite can be free of a void space.

The SbCo—M-type ferrite can be surface-treated (also referred to herein as coated) to aid dispersion into the polymer or polymer precursor, for example, with at least one of a surfactant (such as oleylamine oleic acid), an inorganic material (such as SiO₂, Al₂O₃, and MgO), a silane, a titanate, or a zirconate.

The coating can comprise at least one of a silane coating, a titanate coating, or a zirconate coating. The coating can comprise at least one of phenyltrimethoxysilane, p-chloromethylphenyltrimethoxy silane, aminoethylaminotrimethoxy silane, aminoethylaminopropyltrimethoxy silane, phenyltriethoxysilane, 3,3,3-trifluoropropyl trimethoxysilane, (tridecafluoro-1,1,2,2-tetrahydrodecyl)-1-triethoxysilane, neopentyl(diallyl)oxytridecanoyl titanate, neopentyl(diallyl)oxytri(dioctyl)phosphate titanate, neopentyl(diallyl)oxytri(dioctyl)pyrophosphate zirconate, or neopentyl(diallyl)oxytri(N-ethylenediamino)ethyl zirconate. The coating can comprise a silane coating comprising at least one of an aromatic silane such as phenyltrimethoxysilane or a fluorinated aliphatic alkoxy silane such as (tridecafluoro-1,1,2,2-tetrahydrooctyl)triethoxy silane.

An article can comprise the SbCo—M-type ferrite. The article can be an antenna or an inductor core. The article can be for use in the frequency 0.1 to 4 gigahertz range, or in the 0.5 to 2 gigahertz range. The article can be used for a variety of devices operable within the ultrahigh frequency range, such as a high frequency or microwave antenna, filter, inductor, circulator, or phase shifter. The article can be operable at frequencies greater than or equal to 1 GHz, or at frequencies 1 to 3 GHz. Such articles can be used in commercial and military applications, weather radar, scientific communications, wireless communications, autonomous vehicles, aircraft communications, space communica-

tions, satellite communications, or surveillance. The article can be used for EMI (electromagnetic interference) shielding applications.

As disclosed herein, the SbCo—M-type ferrite can have the general formula: $\text{Me}_{1-x}\text{Sb}_x\text{Co}_{y+x}\text{M}'_y\text{Fe}_{12-x-2y}\text{O}_{19}$, wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3. In the formula, x can be 0.005 to 0.1. In the formula, y can be 1 to 1.2. In the formula, Me can include or can be Ba. In the formula, M' can include or can be Ti. The SbCo—M-type ferrite can have an average grain size of 1 to 100 micrometers, or 5 to 50 micrometers. The SbCo—M-type ferrite can have desirable permeability values over a high frequency range. The SbCo—M-type ferrite can be in the form of a bulk ceramic. A composite can comprise the SbCo—M-type ferrite and a polymer. The composite can be free of a void space. An article can comprise the SbCo—M-type ferrite. An article can comprise the composite. The article can be, for example, a microwave antenna, a filter, an inductor, a circulator, or a phase shifter. The article can be used in various applications including commercial and military applications, weather radar, scientific communications, wireless communications, autonomous vehicles, aircraft communications, space communications, satellite communications, surveillance, or EMI shielding applications.

The following examples are provided to illustrate the present disclosure. The examples are merely illustrative and are not intended to limit devices made in accordance with the disclosure to the materials, conditions, or process parameters set forth therein.

EXAMPLES

In the examples, the magnetic permeability of the resulting ferrite samples was measured using an E4991B Impedance Analyzer commercially available from Keysight Technologies over a frequency of 1 MHz to 1 GHz.

The particle sizes were determined using Horiba LA-910 laser light scattering PSD analyzer or as determined in accordance with ASTM D4464-15. The reported particle size is the median D50 particle size by volume.

Examples 1 and 2: Effect of Antimony on the Co—M-Type Phase Ferrite

Two samples of the Co—M-type phase ferrite with and without antimony were formed by mixing appropriate amounts of BaCO₃, Sb₂O₃, Co₃O₄, TiO₂, and Fe₂O₃ in a wet planetary mill to form a mixture. The mixtures were calcined to a calcination temperature of 1,100° C. for a soak time of 4 hours in air. The calcined ferrite was crushed and sieved through a 40 mesh screen. The coarse particles were ground to form particulates having a median D50 particle size by volume of 0.5 to 10 micrometers in a wet planetary mill. A granulate mixture was formed by mixing the particulates with 0.5 to 5 weight percent of poly(vinyl alcohol) based the total amount of the granulate mixture. The granulate mixture was then compressed to form toroid granules having an outer diameter of 18 millimeters, an inner diameter of 10 millimeters, and a thickness of 3 to 3.5 millimeters at a pressure of 1 metric tons per centimeter squared. The toroid granules were sintered at a sintering temperature of 1,240° C. for 4 hours in air, using a ramp rate: 3° C. per minute and a cooling rate of -3° C. per minute. The Co—M-type phase ferrites with and without antimony had formulae $\text{Ba}_1\text{Co}_{1.1}\text{Ti}_{1.1}\text{Fe}_{9.8}\text{O}_{19}$ and $\text{Ba}_{0.99}\text{Sb}_{0.01}\text{Co}_{11.1}\text{Ti}_{1.1}\text{Fe}_{9.79}\text{O}_{19}$, respectively.

The permeability (solid lines) and the magnetic loss tangent (dashed lines) are shown in FIG. 1 as a function of frequency and specific values of the different compositions are shown in Table 1, where fr stands for the resonant frequency.

TABLE 1

Ferrite Sample	1	2
Antimony	N	Y
μ' at 1 GHz	26	32
μ' at 100 GHz	27	30
$\tan\delta_\mu$ at 100 GHz	0.30	0.22
fr (MHz)	210	300
Snoek Product (GHz)	5.46	9.60

The results show that incorporating an amount of antimony in the M-type ferrite, results in a significant increase in both the permeability and resonance frequency at high frequencies.

Set forth below are non-limiting aspects of the present disclosure.

Aspect 1: A ferrite composition comprising a SbCo—M-type ferrite having the formula $\text{Me}_{1-x}\text{Sb}_x\text{Co}_{y+x}\text{M}'_y\text{Fe}_{12-x-2y}\text{O}_{19}$, wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3.

Aspect 2: The ferrite composition of Aspect 1, wherein y is 1 to 1.2.

Aspect 3: The ferrite composition of any one or more of the preceding aspects, wherein Me is at least Ba.

Aspect 4: The ferrite composition of any one or more of the preceding aspects, wherein M' is at least Ti.

Aspect 5: The ferrite composition of any one or more of the preceding aspects, wherein x is 0.005 to 0.1.

Aspect 6: The ferrite composition of any one or more of the preceding aspects, wherein the ferrite composition has a permeability of greater than or equal to 30, or greater than or equal to 50, or 28 to 55, or 28 to 35 at a frequency of 1 to 300 megahertz in the form of a solid ceramic.

Aspect 7: The ferrite composition of any one or more of the preceding aspects, wherein the ferrite composition has a complex permeability at 200 megahertz of 30 to 40, or 30 to 35; or the SbCo—M-type ferrite can have a complex permeability at 300 megahertz of 20 to 35, or 35 to 30.

Aspect 8: The ferrite composition of any one or more of the preceding aspects, wherein the ferrite composition has a magnetic loss tangent $\tan\delta_\mu$ % of less than or equal to 0.3, less than or equal to 0.1, or 0.01 to 0.3 at a frequency of 1 to 300 megahertz in the form of a solid ceramic.

Aspect 9: The ferrite composition of any one or more of the preceding aspects, wherein the ferrite composition has a resonant frequency of greater than or equal to 250, or 250 to 500 megahertz in the form of a solid ceramic; or wherein the ferrite composition has a Snoek product) of greater than or equal to 8 gigahertz, or greater than or equal to 9 gigahertz, or 9 to 15 gigahertz at a in the form of a solid ceramic.

Aspect 10: A composite comprising a ferrite composition, for example, of any one or more of the preceding aspects and a polymer. The composite can be free of a void space.

Aspect 11: An article comprising a ferrite composition, for example, of any one or more of Aspects 1 to 9 or the composite of Aspect 10.

Aspect 12: The article of Aspect 11, wherein the article is an antenna, filter, inductor, circulator, or phase shifter.

Aspect 13: The article of any one or more of Aspects 11 to 12, wherein the article is a microwave antenna.

Aspect 14: The article of any one or more of Aspects 11 to 13, wherein the article is an antenna operable at a frequency of 1 to 300 megahertz, or 30 to 300 megahertz.

Aspect 15: A method of making a ferrite composition, for example, of any one or more of the preceding aspects comprising: mixing ferrite precursor compounds comprising Me, Fe, Sb, Co, and M'; and sintering the ferrite precursor compounds in an oxygen atmosphere to form the SbCo—M-type ferrite.

Aspect 16: The method of Aspect 15, wherein the ferrite precursor compounds comprise MeCO_3 , Sb_2O_3 , Co_3O_4 , $\text{M}'\text{O}_2$, and Fe_2O_3 .

Aspect 17: The method of Aspect 16, wherein the ferrite precursor compounds comprise 5 to 20 weight percent of MeCO_3 , 0.01 to 20 weight percent of Sb_2O_3 , 1 to 15 weight percent of Co_3O_4 , 0.1 to 10 weight percent of $\text{M}'\text{O}_2$, and 50 to 80 weight percent of Fe_2O_3 ; all based on the total weight of the precursor compounds.

Aspect 18: The method of any one or more of Aspects 15 to 17, wherein the sintering occurs at a sintering temperature of 1,000 to 1,300° C., or 1,200 to 1,250° C. for a sintering time of 1 to 20 hours, or 5 to 12 hours.

Aspect 19: The method of any one or more of Aspects 15 to 18, further comprising calcining the ferrite precursor compounds in air prior to the sintering.

Aspect 20: The method of any one or more of Aspects 15 to 19, further comprising mixing the ferrite precursor compounds with a binder prior to the sintering.

Aspect 21: The method of any one or more of Aspects 15 to 20, further comprising forming the ferrite precursor compounds prior to the sintering.

Aspect 22: A method of making a composite (for example, of Aspect 10) comprising mixing a ferrite composition (for example, of any one or more of Aspects 1 to 9 and optionally formed by the method of any one or more of Aspects 15 to 20) and a polymer to form the composite; and optionally shaping mixture; wherein the mixing optionally occurs at a temperature greater than or equal to the a melting temperature of the polymer.

Aspect 23: A method of making a composite (for example, of Aspect 10) comprising mixing a ferrite composition (for example, of any one or more of Aspects 1 to 9 and optionally formed by the method of any one or more of Aspects 15 to 20) and a polymer precursor; and polymerizing the polymer precursor to form the composite.

The compositions, methods, and articles can alternatively comprise, consist of, or consist essentially of, any appropriate materials, steps, or components herein disclosed. The compositions, methods, and articles can additionally, or alternatively, be formulated so as to be devoid, or substantially free, of any materials (or species), steps, or components, that are otherwise not necessary to the achievement of the function or objectives of the compositions, methods, and articles.

As used herein, “a,” “an,” “the,” and “at least one” do not denote a limitation of quantity, and are intended to cover both the singular and plural, unless the context clearly indicates otherwise. For example, “an element” has the same meaning as “at least one element,” unless the context clearly indicates otherwise. The term “at least one of” means that the list is inclusive of each element individually, as well as combinations of two or more elements of the list, and combinations of at least one element of the list with like elements not named. Also, the term “combination” is inclusive of blends, mixtures, alloys, reaction products, and the like. The term “or” means “and/or” unless clearly indicated otherwise by context. Reference throughout the specification

to “an aspect”, “an embodiment”, “another embodiment”, “some embodiments”, and so forth, means that a particular element (e.g., feature, structure, step, or characteristic) described in connection with the embodiment is included in at least one embodiment described herein, and may or may not be present in other embodiments. In addition, it is to be understood that the described elements may be combined in any suitable manner in the various embodiments.

Unless specified to the contrary herein, all test standards are the most recent standard in effect as of the filing date of this application, or, if priority is claimed, the filing date of the earliest priority application in which the test standard appears.

The endpoints of all ranges directed to the same component or property are inclusive of the endpoints, are independently combinable, and include all intermediate points and ranges. For example, ranges of “up to 25 wt %, or 5 to 20 wt %” is inclusive of the endpoints and all intermediate values of the ranges of “5 to 25 wt %,” such as 10 to 23 wt %, etc.


Unless defined otherwise, technical and scientific terms used herein have the same meaning as is commonly understood by one of skill in the art to which this disclosure belongs.

All cited patents, patent applications, and other references are incorporated herein by reference in their entirety. However, if a term in the present application contradicts or conflicts with a term in the incorporated reference, the term from the present application takes precedence over the conflicting term from the incorporated reference.

While particular embodiments have been described, alternatives, modifications, variations, improvements, and substantial equivalents that are or may be presently unforeseen may arise to applicants or others skilled in the art. Accordingly, the appended claims as filed and as they may be amended are intended to embrace all such alternatives, modifications variations, improvements, and substantial equivalents.

What is claimed is:

1. A ferrite composition comprising a SbCo—M-type ferrite having the formula:



wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 1 to 1.2.

2. The ferrite composition of claim 1, wherein Me is at least Ba and/or wherein M' is at least Ti.

3. The ferrite composition of claim 1, wherein x is 0.005 to 0.1.

4. The ferrite composition of claim 1, wherein the ferrite composition has a permeability of greater than or equal to 30 at a frequency of 1 to 300 megahertz in the form of a solid ceramic.

5. The ferrite composition of claim 1, wherein the ferrite composition has a complex permeability at 200 megahertz of 30 to 40; or the SbCo—M-type ferrite can have a complex permeability at 300 megahertz of 20 to 35.


6. The ferrite composition of claim 1, wherein the ferrite composition has a magnetic loss tangent $\tan \delta_\mu$ of less than or equal to 0.3 at a frequency of 1 to 300 megahertz in the form of a solid ceramic.

7. The ferrite composition of claim 1, wherein the ferrite composition has a resonant frequency of greater than or equal to 250 megahertz in the form of a solid ceramic; or wherein the ferrite composition has a Snoek product of greater than or equal to 8 gigahertz in the form of a solid ceramic.

8. A composite comprising the ferrite composition of claim 1 and a polymer.

9. An article comprising the ferrite composition of claim 1.

10. An article comprising a ferrite composition comprising a SbCo—M-type ferrite having the formula:




wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3, and

wherein the article is an antenna, filter, inductor, circulator, or phase shifter.

11. The article of claim 9 wherein the article is a microwave antenna.

12. The article of claim 9, wherein the article is an antenna operable at a frequency of 1 to 300 megahertz.

13. A method of making a ferrite composition comprising a SbCo—M-type ferrite having the formula:



wherein Me is at least one of Sr, Pb, or Ba; M' is at least one of Ti, Zr, Ru, or Ir; x is 0.001 to 0.3; and y is 0.8 to 1.3,

the method comprising:

mixing ferrite precursor compounds comprising Me, Fe, Sb, Co, and M'; and

sintering the ferrite precursor compounds in an oxygen atmosphere to form the SbCo—M-type ferrite.

14. The method of claim 13, wherein the ferrite precursor compounds comprise MeCO_3 , Sb_2O_3 , Co_3O_4 , $\text{M}'\text{O}_2$, and Fe_2O_3 .

15. The method of claim 14, wherein the ferrite precursor compounds comprise 5 to 20 weight percent of MeCO_3 , 0.01 to 20 weight percent of Sb_2O_3 , 1 to 15 weight percent of Co_3O_4 , 0.1 to 10 weight percent of $\text{M}'\text{O}_2$, and 50 to 80 weight percent of Fe_2O_3 ; all based on the total weight of the precursor compounds.

16. The method of claim 13, wherein the sintering occurs at a sintering temperature of 1,000 to 1,300° C. for a sintering time of 1 to 20 hours.

17. The method of claim 13, further comprising calcining the ferrite precursor compounds in air prior to the sintering.

18. The method of claim 13, further comprising mixing the ferrite precursor compounds with a binder prior to the sintering.

19. The method of claim 13, further comprising forming the ferrite precursor compounds prior to the sintering.

* * * * *