

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402389
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Singh; Gulbagh et al.

Semiconductor arrangement with airgap and method of forming

Abstract

A semiconductor arrangement includes a gate structure disposed between a first source/drain region and a second source/drain region and a first contact disposed over the first source/drain region. The semiconductor arrangement includes a second contact disposed over the second source/drain region and an airgap disposed between the first contact and the second contact and over the gate structure.

Inventors: Singh; Gulbagh (Tainan, TW), Po-Jen; Wang (Taichung, TW), Chuang; Kun-Tsang (Miaoli, TW), Tsai; Tsung-Han (Zhunan Township, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY LIMITED
(Hsin-Chu, TW)

Family ID: 1000008780003

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY LIMITED
(Hsin-Chu, TW)

Appl. No.: 17/869571

Filed: July 20, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220359707 A1	Nov. 10, 2022

Related U.S. Application Data

division parent-doc US 16441200 20190614 US 11417749 child-doc US 17869571

Publication Classification

Int. Cl.: H10D64/66 (20250101); H01L21/02 (20060101); H01L21/28 (20060101); H01L21/285 (20060101); H01L21/311 (20060101); H01L21/764 (20060101); H10D64/62 (20250101); H10D64/68 (20250101)

U.S. Cl.:

CPC H10D64/679 (20250101); H01L21/02167 (20130101); H01L21/28123 (20130101); H01L21/28518 (20130101); H01L21/31116 (20130101); H01L21/764 (20130101); H10D64/62 (20250101); H10D64/68 (20250101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6333255	12/2000	Sekiguchi	257/E21.589	H01L 21/76885
7553756	12/2008	Hayashi et al.	N/A	N/A
8232618	12/2011	Breyta	257/513	H01L 23/5222
2002/0047207	12/2001	Sekiguchi	N/A	N/A
2012/0037962	12/2011	Breyta et al.	N/A	N/A
2016/0141240	12/2015	Saka	257/288	H01L 29/41758
2017/0330832	12/2016	He	N/A	H01L 27/1203

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1832131	12/2005	CN	N/A
105308736	12/2015	CN	N/A
107424968	12/2016	CN	N/A
201603146	12/2015	TW	N/A
201621981	12/2015	TW	N/A
201806126	12/2017	TW	N/A

Primary Examiner: Vu; Hung K

Attorney, Agent or Firm: Cooper Legal Group, LLC

Background/Summary

RELATED APPLICATIONS (1) This application is a divisional of and claims priority to U.S. patent application Ser. No. 16/441,200, titled “SEMICONDUCTOR ARRANGEMENT WITH AIRGAP AND METHOD OF FORMING” and filed on Jun. 14, 2019, which is incorporated herein by reference.

BACKGROUND

(1) A semiconductor arrangement has an off-state capacitance while in an off state. The off-state capacitance includes a device capacitance and a wiring capacitance. The device capacitance is

caused by the capacitances between layers of a device, such as a transistor, within the semiconductor arrangement. The wiring capacitance is caused by the capacitances between layers of a contact structure and the device. High off-state capacitances increase time delay and decrease switching performance of the semiconductor arrangement.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. 1A-1J and 2 are illustrations of cross-sectional views of a semiconductor arrangement at various stages of fabrication, in accordance with some embodiments.

(3) FIG. 3 is an illustration of a cross-sectional view of a semiconductor arrangement comprising an airgap, in accordance with some embodiments.

(4) FIG. 4 is an illustration of a cross-sectional view of a semiconductor arrangement comprising an airgap, in accordance with some embodiments.

(5) FIG. 5 is an illustration of a cross-sectional view of a semiconductor arrangement comprising an airgap, in accordance with some embodiments.

(6) FIG. 6 is an illustration of a cross-sectional view of a semiconductor arrangement comprising an airgap, in accordance with some embodiments.

DETAILED DESCRIPTION

(7) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(8) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(9) As provided herein, in some embodiments a semiconductor arrangement is formed to have an airgap. In some embodiments, the semiconductor arrangement comprises a transistor having a gate structure and a plurality of source/drain regions. In some embodiments, the airgap is formed over the gate structure and between a first contact electrically coupled to a first source/drain region of the semiconductor arrangement and a second contact electrically coupled to a first source/drain region of the semiconductor arrangement. In some embodiments, the airgap is formed over the gate structure and between a first metal structure overlying the first contact and a second metal structure overlying the second contact.

(10) In some embodiments, the airgap comprises air or other suitable gases having a low dielectric constant. In some embodiments, because of the low dielectric constant, wiring capacitances between at least one of the gate structure and the contacts or the gate structure and the metal structures are reduced. In some embodiments, the airgap reduces an off-state capacitance of the semiconductor arrangement by about 40% or more. In some embodiments, reducing the off-state capacitance improves a resistance-capacitance (RC) time delay of the semiconductor arrangement and improves radio frequency (RF) switching of the semiconductor arrangement.

(11) FIGS. 1A-2 are cross-sectional views of a semiconductor arrangement formed with an airgap in accordance with some embodiments. Referring to FIG. 1A, a semiconductor arrangement **100** comprising a first source/drain region **104**, a second source/drain region **106**, and a gate structure **101** disposed over a substrate **103** is provided. The first source/drain region **104**, the second source/drain region **106**, and the gate structure **101** are disposed between isolation structures **102**, such as shallow trench isolation (STI) structures. In some embodiments, a first silicide **108** is disposed over the first source/drain region **104**. In some embodiments, a second silicide **110** is disposed over the second source/drain region **106**. In some embodiments, the first silicide **108** and the second silicide **110** comprise nickel silicide (NiSi) or other suitable material.

(12) In some embodiments, the gate structure **101** comprises a gate dielectric layer **109**, a gate electrode **112**, and a cap layer **114**. In some embodiments, the gate dielectric layer **109** comprises a high-k dielectric material. As used herein, the term “high-k dielectric” refers to the material having a dielectric constant, k , greater than or equal to about 3.9, which is the k value of SiO_2 . The material of the high-k dielectric layer may be any suitable material. Examples of the material of the high-k dielectric layer include but are not limited to Al_2O_3 , HfO_2 , ZrO_2 , La_2O_3 , TiO_2 , SrTiO_3 , LaAlO_3 , Y_2O_3 , $\text{Al}_2\text{O}_3\cdot x\text{N}\cdot y$, $\text{HfO}_2\cdot x\text{N}\cdot y$, $\text{ZrO}_2\cdot x\text{N}\cdot y$, $\text{La}_2\text{O}_3\cdot x\text{N}\cdot y$, $\text{TiO}_2\cdot x\text{N}\cdot y$, $\text{SrTiO}_3\cdot x\text{N}\cdot y$, $\text{LaAlO}_3\cdot x\text{N}\cdot y$, $\text{Y}_2\text{O}_3\cdot x\text{N}\cdot y$, SiON , SiN , a silicate thereof, and an alloy thereof. Each value of x is independently from 0.5 to 3, and each value of y is independently from 0 to 2.

(13) In some embodiments, the gate electrode comprises polysilicon, metal, or other suitable materials. In some embodiments, the cap layer **114** comprises nickel silicide (NiSi) or other suitable material. In some embodiments, sidewall spacers **116** of the gate structure **101** are formed adjacent sidewalls of at least one of the gate dielectric layer **109**, the gate electrode **112**, or the cap layer **114**.

(14) Referring to FIG. 1B, a first etch stop layer (ESL) **118** is formed over at least one of the isolation structures **102**, the first silicide **108**, the second silicide **110**, the sidewall spacers **116**, or the cap layer **114** of the semiconductor arrangement **100**, in accordance with some embodiments. In some embodiments, the first etch stop layer **118** is formed conformally over the at least one of the isolation structures **102**, the first silicide **108**, the second silicide **110**, the sidewall spacers **116**, or the cap layer **114**, such that the first etch stop layer **118** has a substantially uniform thickness. In some embodiments, the first etch stop layer **118** is formed non-conformally over the at least one of the isolation structures **102**, the first silicide **108**, the second silicide **110**, the sidewall spacers **116**, or the cap layer **114**, such that the first etch stop layer **118** has a non-uniform thickness.

(15) In some embodiments, the first etch stop layer **118** comprises a silicon nitride (SiN) or other suitable material. In some embodiments, the first etch stop layer **118** is formed by a deposition process, such as chemical vapor deposition (CVD), physical vapor deposition (PVD), plasma enhanced chemical vapor deposition (PECVD), atomic layer CVD (ALCVD), atomic layer deposition (ALD), a spin-on technology, or other suitable deposition process. In some embodiments, such as where the first silicide **108** and the second silicide **110** are not formed, the first etch stop layer **118** is formed over and contacts the first source/drain region **104** and the second source/drain region **106**.

(16) Referring to FIG. 1C, a protection layer **120** is formed over the first etch stop layer **118** of the

semiconductor arrangement **100**, in accordance with some embodiments. In some embodiments, the protection layer **120** is formed conformally over the first etch stop layer **118**. In some embodiments, the protection layer **120** is formed non-conformally over the first etch stop layer **118** (17) In some embodiments, the protection layer **120** comprises silicon carbide (SiC) or other suitable material. In some embodiments, the protection layer **120** comprises a plurality of dielectric layers. For example, the protection layer **120** may comprise a silicon carbide layer, a silicon oxide layer over the silicon carbide layer, and a second silicon carbide layer over the silicon oxide layer. In some embodiments, the protection layer **120** is formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process. In some embodiments, the protection layer **120** has a thickness in a range from about 100 angstroms to about 1,000 angstroms. In some embodiments, the protection layer **120** generates stress, such as tensile strain or compressive strain, in a channel region between the first source/drain region **104** and the second source/drain region **106** that enhances electron carrier mobility of electrons through the channel region.

(18) In some embodiments, the first etch stop layer **118** is not formed within the semiconductor arrangement **100**. In such embodiments, the protection layer **120** may be formed directly over at least one of the isolation structures **102**, the first silicide **108**, the second silicide **110**, the sidewall spacers **116**, or the cap layer **114**, for example.

(19) Referring to FIG. **1D**, a first dielectric layer **122** is formed over the protection layer **120**, in accordance with some embodiments. In some embodiments, the first dielectric layer **122** comprises a low-k dielectric material. Low-k dielectric materials have a k-value (dielectric constant) lower than about 3.9. Some low-k dielectric materials have a k-value lower than about 3.5 and may have a k-value lower than about 2.5. In some embodiments, the first dielectric layer **122** comprise at least one of Si, O, C, or H, such as SiCOH and SiOC, or other suitable materials. In some embodiments, organic materials such as polymers are used for the first dielectric layer **122**. In some embodiments, the first dielectric layer **122** comprises one or more layers of a carbon-containing material, organo-silicate glass, a porogen-containing material, or combinations thereof. In some embodiments, the first dielectric layer **122** comprises nitrogen. In some embodiments, the first dielectric layer **122** is formed by using, for example, at least one of CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process.

(20) Referring to FIG. **1E**, the first dielectric layer **122**, the protection layer **120**, and the first etch stop layer **118** are etched to define a first recess, and a first contact **124** is formed in the first recess, in accordance with some embodiments. In some embodiments, the first dielectric layer **122**, the protection layer **120**, and the first etch stop layer **118** are etched to also define a second recess, and a second contact **126** is formed in the second recess. In some embodiments, the first dielectric layer **122**, the protection layer **120**, and the first etch stop layer **118** are etched using a single damascene process or a multi-damascene, such as dual damascene process, to define the first recess and the second recess. In some embodiments, the first contact **124** and the second contact **126** are formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process. In some embodiments, a chemical-mechanical planarization (CMP) process is performed after the deposition process to remove excess material deposited during the deposition process.

(21) In some embodiments, the first contact **124** is formed over the first source/drain region **104** and is in contact with the first silicide **108**. In this way, the first contact **124** provides electrical connectivity to the first source/drain region **104**. In some embodiments, the first contact **124** is formed to be in contact with the first etch stop layer **118** and the protection layer **120**. In some embodiments, the second contact **126** is formed over the second source/drain region **106** and is in contact with the second silicide **110**. In this way, the second contact **126** provides electrical connectivity to the second source/drain region **106**. In some embodiments, the second contact **126** is formed to be in contact with the first etch stop layer **118** and the protection layer **120**. In some

embodiments, the first contact **124** and the second contact **126** comprise a conductive material, such as copper or other suitable material.

(22) Referring to FIG. **1F**, a second etch stop layer **128** is formed over the first dielectric layer **122** of the semiconductor arrangement **100**, in accordance with some embodiments. In some embodiments, the second etch stop layer **128** is formed over the first contact **124** and the second contact **126** of the semiconductor arrangement **100**. In some embodiments, the second etch stop layer **128** is formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process.

(23) In some embodiments, the second etch stop layer **128** comprises a silicon nitride (SiN), silicon carbide (SiC), or other suitable material. In some embodiments, the second etch stop layer **128** comprises a same material composition as the first etch stop layer **118**. In some embodiments, the second etch stop layer **128** comprises a same material composition as the protection layer **120**. In some embodiments, a material composition of the second etch stop layer **128** is different than a material composition of the first etch stop layer **118** and is different than a material composition of the protection layer **120**.

(24) Referring to FIG. **1G**, a second dielectric layer **130** is formed over the second etch stop layer **128**, in accordance with some embodiments. In some embodiments, the second dielectric layer **130** is formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process.

(25) In some embodiments, the second dielectric layer **130** comprises a low-k dielectric material. In some embodiments, the first dielectric layer **122** and the second dielectric layer **130** comprise a same material composition. In some embodiments, the first dielectric layer **122** comprises a first material composition and the second dielectric layer **130** comprises a second material composition different than the first material composition.

(26) Referring to FIG. **1H**, the second dielectric layer **130** and the second etch stop layer **128** are etched to define a third recess and a first metal structure **132** is formed within the third recess, in accordance with some embodiments. In some embodiments, the second dielectric layer **130** and the second etch stop layer **128** are also etched to define a fourth recess and a second metal structure **134** is formed within the fourth recess. In some embodiments, the second dielectric layer **130** and the second etch stop layer **128** are etched using a single damascene process or a multi-damascene, such as dual damascene process, to define the third recess and the fourth recess. In some embodiments, the first metal structure **132** and the second metal structure **134** are formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process. In some embodiments, a CMP process is performed after the deposition process to remove excess material deposited during the deposition process.

(27) In some embodiments, the first contact **124** is exposed through the third recess during the etching of the second dielectric layer **130** and the second etch stop layer **128**, and the first metal structure **132** is formed to contact the first contact **124**. In some embodiments, the second contact **126** is exposed through the fourth recess during the etching of the second dielectric layer **130** and the second etch stop layer **128**, and the second metal structure **134** is formed to contact the second contact **126**.

(28) In some embodiments, the first metal structure **132** and the second metal structure **134** are metal lines within a metal one (M1) back end of line (BEOL) layer of the semiconductor arrangement **100**. In some embodiments, the first metal structure **132** and the second metal structure **134** comprise a conductive material, such as copper or other suitable material.

(29) In some embodiments, a third etch stop layer **136** is formed over the second dielectric layer **130** of the semiconductor arrangement **100** after the first metal structure **132** and the second metal structure **134** are formed. In some embodiments, the third etch stop layer **136** is formed over the first metal structure **132** and the second metal structure **134**. In some embodiments, the third etch stop layer **136** comprises a silicon nitride (SiN), silicon carbide (SiC), or other suitable material.

(30) While in the illustrated embodiments, the third etch stop layer **136** is formed over the first metal structure **132** and the second metal structure **134**, in some embodiments, the third etch stop layer **136** is formed laterally adjacent the first metal structure **132** and the second metal structure **134**. For example, in some embodiments, the second dielectric layer **130** is recessed to expose a portion of a sidewall of the first metal structure **132** and a portion of the sidewall of the second metal structure **134**, and the third etch stop layer **136** is formed in the recess to contact the portion of the sidewall of the first metal structure **132** and the portion of the sidewall of the second metal structure **134** (not shown).

(31) Referring to FIG. **1I**, a first etch process is performed through at least one of the third etch stop layer **136**, the second dielectric layer **130**, the second etch stop layer **128**, and the first dielectric layer **122** of the semiconductor arrangement **100**, in accordance with some embodiments. In some embodiments, the first etch process forms a cavity **138** over the gate structure **101**. In some embodiments, the first etch process forms the cavity **138** between the first contact **124** and the second contact **126**. In some embodiments, the first etch process forms the cavity **138** between the first metal structure **132** and the second metal structure **134**. In some embodiments, the first etch process etches to and exposes a first portion of the protection layer **120**, as illustrated in FIG. **1I**. In some embodiments, the first etch process is terminated before the protection layer **120** is exposed, and thus a portion of the first dielectric layer **122** remains between a bottom of the cavity **138** and the protection layer **120**. In an embodiment, the first etch process comprises a dry etch process, such as a plasma etch or other suitable etch.

(32) In the illustrated embodiment, the cavity **138** is defined by substantially vertical sidewalls of the first dielectric layer **122**, the second etch stop layer **128**, the second dielectric layer **130**, and the third etch stop layer **136**. However, other shapes for the cavity **138** are contemplated. Thus, the cavity **138** need not be defined by substantially vertical sidewalls of the first dielectric layer **122**, the second etch stop layer **128**, the second dielectric layer **130**, and the third etch stop layer **136**, but rather can be defined by tapered or curved sidewalls, for example, of at least one of the first dielectric layer **122**, the second etch stop layer **128**, the second dielectric layer **130**, or the third etch stop layer **136**, for example.

(33) Referring to FIG. **1J**, a second etch process is performed through the cavity **138** to create an airgap **140** within the semiconductor arrangement **100**, in accordance with some embodiments. In some embodiments, the second etch process is performed to remove a portion of the first dielectric layer **122** between the first contact **124** and the second contact **126**. In some embodiments, the second etch process is performed to remove a portion of the second dielectric layer **130** between the first metal structure **132** and the second metal structure **134**. In some embodiments, the second etch process exposes a second portion of the protection layer. In some embodiments, the second etch process exposes a sidewall of at least one of the first contact **124** or the second contact **126**.

(34) In some embodiments, the second etch process can be performed to create various shapes and sizes of airgaps within the semiconductor arrangement **100**, which will be later described in connection with FIGS. **2-7**. The airgap **140** can comprise any shape or size, and thus can be formed to be smaller, larger, or a different shape than what is depicted in FIG. **1J**. In some embodiments, the second etch process comprises a wet etch process, such as a chemical etch, or a combination of a dry etch process and a wet etch process. In some embodiments, the protection layer **120** protects structures and layers underlying the protection layer **120** from being damaged by the second etch process. In some embodiments, the protection layer **120** stops the second etch process from etching the first etch stop layer **118** and the gate structure **101**, and thus protects such devices and layers of the semiconductor arrangement **100**.

(35) In some embodiments, at least a portion of the first dielectric layer **122** between the first contact **124** and the second contact **126** remains after the second etch process. For example, a portion of the first dielectric layer **122** adjacent at least one of a sidewall of the first contact **124**, a sidewall of the second contact **126**, a top surface of the protection layer **120**, or a bottom surface of

the second etch stop layer **128** may remain after the second etch process. In some embodiments, at least a portion of the second dielectric layer **130** between the first metal structure **132** and the second metal structure **134** remains after the second etch process. For example, a portion of the second dielectric layer **130** adjacent at least one of a sidewall of the first metal structure **132**, a sidewall of the second metal structure **134**, a top surface of the second etch stop layer **128**, or a bottom surface of the third etch stop layer **136** may remain after the second etch process.

(36) Moreover, while the illustrated embodiment provides that the first etch process and second etch process are performed after the formation of the third etch stop layer **136**, in some embodiments, the first etch process and the second etch process are performed before the third etch stop layer **136** is formed. Thus, in some embodiments, the first etch process and second etch process are performed while a top surface of the second dielectric layer **130** is exposed.

(37) In some embodiments, a width, or critical dimension (CD), of the airgap **140** is non-uniform. For example, the width of the airgap **140** may decrease moving in a direction from the substrate **103** toward the third etch stop layer **136**. Moreover, in some embodiments, the width of the airgap **140** may vary between layers in which the airgap **140** is formed. For example, the width **141** of the airgap **140** formed in the first dielectric layer **122** may be greater than the width **152** of the airgap **140** formed in the second etch stop layer **128**. Thus, the width **141** of the airgap **140** below the second etch stop layer **128** may be greater than the width **152** of the airgap **140** adjacent the second etch stop layer **128**. As another example, the width **153** of the airgap **140** formed in the second dielectric layer **130** may be greater than the width **152** of the airgap **140** formed in the second etch stop layer **128**. Thus, the width **153** of the airgap **140** above the second etch stop layer **128** may be greater than the width **152** of the airgap **140** adjacent the second etch stop layer **128**.

(38) Referring to FIG. 2, a third dielectric layer **202** is formed over the third etch stop layer **136** after the airgap **140** has been formed, in accordance with some embodiments. In some embodiments, a deposition process, such as a PVD process is performed to form the third dielectric layer **202**. In some embodiments, due to at least one of the size or width **204** of the opening or properties of materials being used to form the third dielectric layer **202** in the third etch stop layer **136**, the third dielectric layer **202** pinches off during the deposition process, resulting in the airgap **140** being closed or sealed prior to the dielectric material of the third dielectric layer **202** filling the airgap **140**. In some embodiment, the third dielectric layer **202** seals the airgap **140** and trap gases comprised within the airgap **140**. In some embodiments, during the deposition process, such as during the PVD process, and prior to the third dielectric layer **202** pinching off, a portion of the third dielectric layer **202** is deposited in the airgap **140** and attaches to one or more of the layers defining the airgap **140**. For example, portions of the third dielectric layer **202** may attach to at least one of a sidewall of the first metal structure **132**, a sidewall of second metal structure **134**, a sidewall of the second dielectric layer **130** if a portion of the second dielectric layer **130** remains present between the airgap **140** and the first metal structure **132** or second metal structure **134**, a sidewall of the first contact **124**, a sidewall of the second contact **126**, a surface of the first dielectric layer **122** if the first dielectric layer **122** remains present between the airgap **140** and at least one of the first contact **124**, the second contact **126** or the protection layer **120**, a top surface of the protection layer **120**, a bottom surface of the second etch stop layer **128**, a top surface of the second etch stop layer **128**, or a bottom surface of the third etch stop layer **136**. In such embodiments, the thickness of the portion of the third dielectric layer **202** may vary within the airgap **140**. Thus, the third dielectric layer **202** may not be uniformly deposited in the airgap **140**.

(39) In some embodiments, a dielectric material of the third dielectric layer **202** is the same as the dielectric material of the first dielectric layer **122**. In some embodiments, the dielectric material of the third dielectric layer **202** is the same as the dielectric material of the second dielectric layer **130**. In some embodiments, the dielectric material of the third dielectric layer **202** is different than the dielectric material of the first dielectric layer **122**. In some embodiments, the dielectric material of the third dielectric layer **202** is different than the dielectric material of the second dielectric layer

130.

(40) In some embodiments, such as where a remnant of the first dielectric layer **122** remains between the airgap **140** and at least one of the first contact **124**, the second contact **126**, the protection layer **120**, or the second etch stop layer **128**, the third dielectric layer **202** may be formed over the remnant of the first dielectric layer **122** such that the remnant of the first dielectric layer **122** separates the at least one of the first contact **124**, the second contact **126**, the protection layer **120**, or the second etch stop layer **128** from the third dielectric layer **202**. In some embodiments, such as where a remnant of the second dielectric layer **130** remains between the airgap **140** and at least one of the first metal structure **132**, the second metal structure **134**, the second etch stop layer **128**, or the third etch stop layer **136**, the third dielectric layer **202** may be formed over the remnant of the second dielectric layer **130** such that the remnant of the second dielectric layer **130** separates the at least one of the first metal structure **132**, the second metal structure **134**, the second etch stop layer **128**, or the third etch stop layer **136** from the third dielectric layer **202**.

(41) In some embodiments, the third dielectric layer **202** and the third etch stop layer **136** are etched to define a fifth recess and a third metal structure **206** is formed within the fifth recess, in accordance with some embodiments. In some embodiments, the first metal structure **132** is exposed through the fifth recess and the third metal structure **206** is formed to contact the first metal structure **132**. In some embodiments, the third dielectric layer **202** and the third etch stop layer **136** are also etched to define a sixth recess and a fourth metal structure **210** is formed within the sixth recess. In some embodiments, the second metal structure **134** is exposed through the sixth recess and the fourth metal structure **210** is formed to contact the second metal structure **134**.

(42) In some embodiments, the third dielectric layer **202** and the third etch stop layer **136** are etched using a single damascene process or a multi-damascene, such as dual damascene process, to define the fifth recess and the sixth recess. In some embodiments, the third metal structure **206** and the fourth metal structure **210** are formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process. In some embodiments, a CMP process is performed after the deposition process to remove excess material deposited during the deposition process.

(43) In some embodiments, the third metal structure **206** and the fourth metal structure **210** are at least one of vias or metal lines within a metal two (M2) back end of line (BEOL) layer. In some embodiments, the third metal structure **206** and the fourth metal structure **210** comprise a conductive material, such as copper or other suitable material. In some embodiments, the third metal structure **206** and the fourth metal structure **210** have a same material composition as the first metal structure **132** and the second metal structure **134**. In some embodiments, a material composition of the third metal structure **206** and the fourth metal structure **210** is different than a material composition of the first metal structure **132** and the second metal structure **134**.

(44) In some embodiments, the airgap **140** is formed to replace at least some dielectric material of the first dielectric layer **122** between the first contact **124** and the second contact **126** and over the gate structure **101**. In some embodiments, the airgap **140** comprises air or other suitable gases, which may have a lower dielectric constant than the dielectric constant of the first dielectric layer **122**. Capacitance between two elements is a function of a dielectric constant of a material separating the two elements, and thus a lower dielectric constant of the material separating the two elements will result in a lower capacitance between the two elements.

(45) In some embodiments, the removal of a portion of the first dielectric layer **122** and formation of the airgap **140** will reduce wiring capacitances within the semiconductor arrangement **100**. In some embodiments, a first-contact-to-gate capacitance **144** between the first contact **124** and the gate structure **101** when the airgap **140** is present between the first contact **124** and the gate structure **101** will be lower than the first-contact-to-gate capacitance **144** between the first contact **124** and the gate structure **101** when the airgap **140** is not present between the first contact **124** and the gate structure **101** and instead the first dielectric layer **122** fills the space between the first

contact **124** and the gate structure **101**. In some embodiments, a second-contact-to-gate capacitance **150** between the second contact **126** and the gate structure **101** when the airgap **140** is present between the second contact **126** and the gate structure **101** will be lower than the second-contact-to-gate capacitance **150** between the second contact **126** and the gate structure **101** when the airgap **140** is not present between the second contact **126** and the gate structure **101** and instead the first dielectric layer **122** fills the space between the second contact **126** and the gate structure **101**.

(46) In some embodiments, a first-metal-structure-to-gate capacitance **146** between the first metal structure **132** and the gate structure **101** when the airgap **140** is present between the first metal structure **132** and the gate structure **101** will be lower than the first-metal-structure-to-gate capacitance **146** between the first metal structure **132** and the gate structure **101** when the airgap **140** is not present between the first metal structure **132** and the gate structure **101** and instead the first dielectric layer **122** fills the space between the first metal structure **132** and the gate structure **101**. In some embodiments, a second-metal-structure-to-gate capacitance **148** between the second metal structure **134** and the gate structure **101** when the airgap **140** is present between the second metal structure **134** and the gate structure **101** will be lower than the second-metal-structure-to-gate capacitance **148** between the second metal structure **134** and the gate structure **101** when the airgap **140** is not present between the second metal structure **134** and the gate structure **101** and instead the first dielectric layer **122** fills the space between the second metal structure **134** and the gate structure **101**.

(47) In some embodiments, the airgap **140** is formed to replace at least some of the dielectric material of the second dielectric layer **130** between the first metal structure **132** and the second metal structure **134** of the semiconductor arrangement **100**. In some embodiments, a metal-structure-to-metal-structure capacitance **142** between the first metal structure **132** and the second metal structure **134** when the airgap **140** is present between the first metal structure **132** and the second metal structure **134** will be lower than the metal-structure-to-metal-structure capacitance **142** between the first metal structure **132** and the second metal structure **134** when the airgap **140** is not present between the first metal structure **132** and the second metal structure **134** and instead the second dielectric layer **130** fills the space between the first metal structure **132** and the second metal structure **134**.

(48) An off-state capacitance of the semiconductor arrangement **100** is a function of the wiring capacitance and a device capacitance of the semiconductor arrangement **100**. In some embodiments, the device capacitance is a function of at least one of a gate-to-source/drain capacitance between the gate structure **101** and the first source/drain region **104**, a gate-to-source/drain capacitance between the gate structure **101** and the second source/drain region **106**, a source/drain-to-substrate capacitance between the first source/drain region **104** and the substrate **103** of the semiconductor arrangement **100**, or a source/drain-to-substrate capacitance between the second source/drain region **106** and the substrate **103** of the semiconductor arrangement **100**. In some embodiments, the wiring capacitance is a function of at least one of the first-contact-to-gate capacitance **144**, the second-contact-to-gate capacitance **150**, the first-metal-structure-to-gate capacitance **146**, the second-metal-structure-to-gate capacitance **148**, or the metal-structure-to-metal-structure capacitance **142**.

(49) Because the airgap **140** reduces the wiring capacitance of the semiconductor arrangement **100**, the off-state capacitance of the semiconductor arrangement **100** is reduced. In some embodiments, reducing the off-state capacitance of the semiconductor arrangement **100** will reduce a time delay of the semiconductor arrangement **100**, such as a resistance-capacitance (RC) time delay of the semiconductor arrangement **100**. In some embodiments, reducing the off-state capacitance of the semiconductor arrangement **100** will improve switch functionality of the semiconductor arrangement **100**, such as radio frequency (RF) switching of the semiconductor arrangement **100**. Many radio frequency front end modules (RF-FEM) require low off-state capacitance, and thus the airgap **140** will reduce the off-state capacitance of the semiconductor arrangement **100** so that the

semiconductor arrangement **100** can be used for radio frequency front end modules and will provide improved high frequency features for the radio frequency front end modules, for example. (50) In some embodiments where the airgap **140** is formed between the first metal structure **132** and the second metal structure **134**, between the first contact **124** and the gate structure **101** and between the second contact **126** and the gate structure **101**, as illustrated by FIG. 2, the off-state capacitance is reduced by about 40% or more. This is because about 45% or more of the off-state capacitance of the semiconductor arrangement **100** is from the wiring capacitances between the first metal structure **132** and the second metal structure **134**, between the first contact **124** and the gate structure **101**, between the second contact **126** and the gate structure **101**, between the first metal structure **132** and the gate structure **101**, and between the second metal structure **134** and the gate structure **101**.

(51) FIG. 3 is a cross-sectional view of a semiconductor arrangement **300** formed with an airgap **302**, in accordance with some embodiments. The semiconductor arrangement **300** differs from the semiconductor arrangement **100** illustrated in FIGS. 1A-2 in that the airgap **302** is separated from the protection layer **120** by the first dielectric layer **122**. In some embodiments, to form the semiconductor arrangement **300**, when performing the first etch process, as described with respect to FIG. 1I, the cavity **138** is formed to extend merely through a portion, such as a top half, of the first dielectric layer **122**, and the protection layer **120** remains concealed by the first dielectric layer **122**. The semiconductor arrangement **300** also differs from the semiconductor arrangement **100** illustrated in FIGS. 1A-2 in that the first etch stop layer **118** is not present. Thus, the protection layer **120** is formed to contact the isolation structures **102**, the first silicide **108**, the sidewall spacers **116**, the cap layer **114**, and the second silicide **110**.

(52) FIG. 4 is a cross-sectional view of a semiconductor arrangement **400** formed with an airgap **402**, in accordance with some embodiments. The semiconductor arrangement **400** differs from the semiconductor arrangement **300** illustrated in FIG. 3 in that the protection layer **120** is formed over the first etch stop layer **118**.

(53) FIG. 5 is a cross-sectional view of a semiconductor arrangement **500** formed with an airgap **502**, in accordance with some embodiments. The semiconductor arrangement **500** differs from the semiconductor arrangement **400** illustrated in FIG. 4 in that an oxide layer **504** is disposed between the first etch stop layer **118** and the protection layer **120**. In some embodiments, the oxide layer **504** comprises silicon oxide or silicon oxynitride. In some embodiments, the oxide layer **504** is formed by depositing an oxide material over the first etch stop layer **118** prior to forming the protection layer **120** using deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other suitable deposition process. In some embodiments, the oxide layer **504** is formed from native oxide caused by the exposure of the underlying first etch stop layer **118** to oxygen.

(54) FIG. 6 is a cross-sectional view of a semiconductor arrangement **600** formed with an airgap **618** according to some embodiments. The semiconductor arrangement **600** differs from the semiconductor arrangement **100** illustrated in FIG. 2 in that a fourth etch stop layer **602**, a fourth dielectric layer **604**, a fifth etch stop layer **608**, and a fifth dielectric layer **610** are formed over the third dielectric layer **202**. Moreover, the semiconductor arrangement **600** comprises a fifth metal structure **606**, a sixth metal structure **612**, a seventh metal structure **614**, and an eighth metal structure **616**.

(55) In some embodiments, the fourth dielectric layer **604** and the fourth etch stop layer **602** are etched to form a seventh recess in which the fifth metal structure **606** is formed and a eighth recess in which the seventh metal structure **614** is formed. In some embodiments, the fourth dielectric layer **604** and the fourth etch stop layer **602** are etched using a single damascene process or a multi-damascene, such as dual damascene process, to define the first recess and the second recess. In some embodiments, fifth metal structure **606** and the seventh metal structure **614** are formed by a deposition process, such as CVD, PVD, PECVD, ALCVD, ALD, a spin-on technology, or other

suitable deposition process. In some embodiments, a chemical-mechanical planarization (CMP) process is performed after the deposition process to remove excess material deposited during the deposition process.

(56) In some embodiments, after the fifth metal structure **606** and the seventh metal structure **614** are formed, the fifth etch stop layer **608** is formed. Then, the first etch process is performed as described with respect to FIG. **1I**. In some embodiments, the first etch process etches through the fifth etch stop layer **608**, the fourth dielectric layer **604**, the fourth etch stop layer **602**, the third dielectric layer **202**, the third etch stop layer **136**, the second dielectric layer **130**, the second etch stop layer **128**, and the first dielectric layer **122**. In some embodiments, the second etch process is performed as described with respect to FIG. **1J** to form the airgap **618**. While the illustrated embodiments illustrate the second etch process removing substantially all of the dielectric materials between the metal structures **132**, **134**, **206**, **210**, **612**, **616** and the contacts **124**, **126**, in some embodiments at least some dielectric material remains between at least one of the metal structures **132**, **134**, **206**, **210**, **612**, **616** and the contacts **124**, **126**. In some embodiments, an amount of dielectric material that remains is a function of the dielectric material being removed and a height between etch stop layers **128**, **136**, **602**, **608** or between the second etch stop layer **128** and the protection layer **120**. For example, an amount of the dielectric layer **604** that remains laterally between the fifth metal structure **606** and the airgap **618** may be greater than an amount of the third dielectric layer **202** that remains laterally between the third metal structure **206** and the airgap **618** due to a height **620** between the third etch stop layer **136** and the fourth etch stop layer **602** being greater than a height **622** between the fourth etch stop layer **602** and the fifth etch stop layer **608**.

(57) In some embodiments, after the airgap **618** is formed, the fifth dielectric layer **610** is formed over the airgap **618** and pinches off to seal the airgap **618**. In some embodiments, the fifth dielectric layer **610** is etched to form a ninth recess in which the sixth metal structure **612** is formed and a tenth recess in which the eighth metal structure **616** is formed. In some embodiments, the sixth metal structure **612** and the eighth metal structure **616** are at least one of vias or metal lines within a metal three (M3) back end of line (BEOL) layer.

(58) In some embodiments, a semiconductor arrangement is provided. The semiconductor arrangement includes a gate structure disposed between a first source/drain region and a second source/drain region. The semiconductor arrangement includes a first contact disposed over the first source/drain region. The semiconductor arrangement includes a second contact over the second source/drain region. The semiconductor arrangement includes an airgap disposed between the first contact and the second contact and over the gate structure. In some embodiments, the semiconductor arrangement includes a protection layer disposed between the gate structure and the airgap. In some embodiments, a sidewall of the first contact is in contact with the protection layer. In some embodiments, the semiconductor arrangement includes a dielectric layer disposed over the gate structure and disposed between the gate structure and the airgap. In some embodiments, the dielectric layer is disposed between the first contact and the airgap. In some embodiments, the semiconductor arrangement includes a protection layer disposed between the gate structure and the dielectric layer. In some embodiments, a sidewall of the first contact is in contact with the protection layer. In some embodiments, the semiconductor arrangement includes a first metal structure disposed over the first contact and interfacing with the first contact and a second metal structure disposed over the second contact and interfacing with the second contact. In some embodiments, the semiconductor arrangement includes an etch stop layer. In some embodiments, the airgap extends through the etch stop layer, the airgap has a first width below the etch stop layer and a second width adjacent the etch stop layer, and the first width is greater than the second width. In some embodiments, the airgap is disposed between the first metal structure and the second metal structure. In some embodiments, the semiconductor arrangement includes a dielectric material disposed over the airgap and between the first metal structure and the second metal structure.

(59) In some embodiments, a semiconductor arrangement is provided. The semiconductor

arrangement includes a gate structure disposed between a first source/drain region and a second source/drain region. The semiconductor arrangement includes an etch stop layer disposed over the gate structure. The semiconductor arrangement includes a protection layer disposed over the etch stop layer. The semiconductor arrangement includes a second etch stop layer, wherein an airgap is disposed between the protection layer and the second etch stop layer. In some embodiments, the semiconductor arrangement includes a dielectric layer disposed over the protection layer. In some embodiments, the airgap is disposed between the dielectric layer and the second etch stop layer. In some embodiments, the semiconductor arrangement includes a contact disposed over the first source/drain region. In some embodiments, the airgap is separated from the contact by the dielectric layer. In some embodiments, the protection layer includes silicon carbide.

(60) In some embodiments, a method for forming a semiconductor arrangement is provided. The method includes forming a gate structure over a substrate and forming a protection layer over the gate structure. The method includes forming a first dielectric layer over the protection layer and performing a first etch process to expose a first portion of the protection layer. The method includes forming a second dielectric layer over the first dielectric layer, wherein an airgap is defined between the first portion of the protection layer and the second dielectric layer. In some embodiments, the method includes performing a second etch process to expose a second portion of the protection layer prior to forming the second dielectric layer. In some embodiments, the method includes forming a first contact through the first dielectric layer, wherein the second etch exposes a sidewall of the first contact. In some embodiments, forming the second dielectric layer includes forming the second dielectric layer to contact with the sidewall of the first contact. In some embodiments, the method includes forming an etch stop layer over the gate structure, wherein forming the protection layer includes forming the protection layer over the etch stop layer.

(61) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

(62) Various operations of embodiments are provided herein. The order in which some or all of the operations are described should not be construed to imply that these operations are necessarily order dependent. Alternative ordering will be appreciated having the benefit of this description. Further, it will be understood that not all operations are necessarily present in each embodiment provided herein. Also, it will be understood that not all operations are necessary.

(63) It will be appreciated that layers, features, elements, etc. depicted herein are illustrated with particular dimensions relative to one another, such as structural dimensions or orientations, for example, for purposes of simplicity and ease of understanding and that actual dimensions of the same differ substantially from that illustrated herein, in one or more embodiments. Additionally, a variety of techniques exist for forming the layers, features, elements, etc. mentioned herein, such as etching techniques, implanting techniques, doping techniques, spin-on techniques, sputtering techniques such as magnetron or ion beam sputtering, growth techniques, such as thermal growth or deposition techniques such as CVD, PVD, PECVD, or ALD, for example.

(64) Moreover, “exemplary” is used herein to mean serving as an example, instance, illustration, etc., and not necessarily as advantageous. As used in this application, “or” is intended to mean an inclusive “or” rather than an exclusive “or”. In addition, “a” and “an” as used in this application and the appended claims are generally to be construed to mean “one or more” unless specified otherwise or clear from context to be directed to a singular form. Also, at least one of A and B and/or the like generally means A or B or both A and B. Furthermore, to the extent that “includes”,

“having”, “has”, “with”, or variants thereof are used, such terms are intended to be inclusive in a manner similar to the term “comprising”. Also, unless specified otherwise, “first,” “second,” or the like are not intended to imply a temporal aspect, a spatial aspect, an ordering, etc. Rather, such terms are merely used as identifiers, names, etc. for features, elements, items, etc. For example, a first element and a second element generally correspond to element A and element B or two different or two identical elements or the same element.

(65) Also, although the disclosure has been shown and described with respect to one or more implementations, equivalent alterations and modifications will occur to others skilled in the art based upon a reading and understanding of this specification and the annexed drawings. The disclosure comprises all such modifications and alterations and is limited only by the scope of the following claims. In particular regard to the various functions performed by the above described components (e.g., elements, resources, etc.), the terms used to describe such components are intended to correspond, unless otherwise indicated, to any component which performs the specified function of the described component (e.g., that is functionally equivalent), even though not structurally equivalent to the disclosed structure. In addition, while a particular feature of the disclosure may have been disclosed with respect to only one of several implementations, such feature may be combined with one or more other features of the other implementations as may be desired and advantageous for any given or particular application.

Claims

1. A method of forming a semiconductor arrangement, comprising: forming a gate structure over a substrate; forming a protection layer over the gate structure; forming a first dielectric layer over the protection layer; defining a recess in the first dielectric layer and the protection layer, wherein the recess overlies a source/drain region and the protection layer is exposed through the recess; forming a contact in the recess; performing a first etch process after forming the contact to define a cavity centered on the gate structure and exposing a first portion of the protection layer; performing a second etch process to expose a second portion of the protection layer; and forming a second dielectric layer over the first dielectric layer after performing the second etch process, wherein an airgap is defined between the first portion of the protection layer and the second dielectric layer.
2. The method of claim 1, wherein the second etch process exposes a sidewall of the contact.
3. The method of claim 2, wherein forming the second dielectric layer comprises forming the second dielectric layer to contact the sidewall of the contact.
4. The method of claim 1, comprising: forming an etch stop layer over the gate structure, wherein forming the protection layer comprises forming the protection layer over the etch stop layer.
5. The method of claim 1, comprising, before performing the first etch process: forming an etch stop layer over the first dielectric layer; and forming a third dielectric layer over the etch stop layer.
6. The method of claim 5, wherein performing the first etch process comprises etching the first dielectric layer, the etch stop layer, and the third dielectric layer.
7. The method of claim 6, wherein the second etch process further etches the first dielectric layer and the third dielectric layer.
8. The method of claim 7, wherein, after the second etch process, a width of the airgap laterally adjacent the third dielectric layer is greater than a width of the airgap laterally adjacent the etch stop layer.
9. The method of claim 1, wherein the second dielectric layer pinches off the airgap, and the second dielectric layer is disposed below the airgap and above the airgap.
10. A method of forming a semiconductor arrangement, comprising: forming a gate structure over a substrate; forming a protection layer over the gate structure; forming a first dielectric layer over the protection layer; forming a contact in the first dielectric layer and over a source/drain region, wherein the contact contacts a sidewall of the protection layer; forming an etch stop layer over the

first dielectric layer; forming a second dielectric layer over the etch stop layer; and performing an etch process to define an airgap in the first dielectric layer, the etch stop layer, and the second dielectric layer, wherein after the etch process, a width of the airgap laterally adjacent the second dielectric layer is greater than a width of the airgap laterally adjacent the etch stop layer.

11. The method of claim 10, wherein a width of the airgap laterally adjacent the first dielectric layer is greater than the width of the airgap laterally adjacent the etch stop layer.

12. The method of claim 10, wherein a portion of the first dielectric layer is disposed between the airgap and the protection layer after the etch process.

13. The method of claim 10, wherein performing the etch process comprises: performing a first etch process that is configured to etch vertically at a faster rate than horizontally; and performing a second etch process after the first etch process that is configured to etch horizontally at a faster rate than vertically.

14. The method of claim 10, comprising: forming a third dielectric layer that pinches off the airgap, wherein the third dielectric layer is disposed below the airgap and above the airgap.

15. The method of claim 10, comprising: forming a second etch stop layer over the gate structure and laterally coincident with the gate structure prior to forming the protection layer.

16. A method of forming a semiconductor arrangement, comprising: forming a gate structure over a substrate; forming a protection layer over the gate structure; forming a first dielectric layer over the protection layer; performing an etch process to remove a portion of the first dielectric layer, wherein an airgap is defined by the etch process and the airgap is laterally coincident with the gate structure; and forming a second dielectric layer over the first dielectric layer, wherein: the second dielectric layer pinches off the airgap, and the second dielectric layer is formed below the airgap and above the airgap.

17. The method of claim 16, wherein performing the etch process comprises: performing a first etch process that is configured to etch vertically at a faster rate than horizontally; and performing a second etch process after the first etch process that is configured to etch horizontally at a faster rate than vertically.

18. The method of claim 16, comprising, before performing the etch process: forming an etch stop layer over the first dielectric layer; and forming a third dielectric layer over the etch stop layer.

19. The method of claim 18, wherein, after the etch process, a width of the airgap laterally adjacent the third dielectric layer is greater than a width of the airgap laterally adjacent the etch stop layer.

20. The method of claim 16, comprising: forming an etch stop layer over the gate structure, wherein forming the protection layer comprises forming the protection layer over the etch stop layer.
