

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12389638
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	More; Shahaji B. et al.

Method of forming fully strained channels

Abstract

A method includes forming an N well and a P well in a substrate; depositing a first layer having silicon over the N well and the P well; depositing a first dielectric layer over the first layer; forming a resist pattern over the first dielectric layer, the resist pattern providing an opening directly above the N well; etching the first dielectric layer and the first layer through the opening, leaving a first portion of the first layer over the N well; removing the resist pattern; and epitaxially growing a second layer having silicon germanium (SiGe) over the first portion of the first layer. The epitaxially growing the second layer includes steps of (a) performing a baking process, (b) depositing a silicon seed layer, and (c) depositing a SiGe layer over the silicon seed layer, wherein the steps (a), (b), and (c) are performed under about a same temperature.

Inventors: More; Shahaji B. (Hsinchu, TW), Kuan; Shu (Keelung, TW), Lee; Cheng-Han (New Taipei, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsin-Chu, TW)

Family ID: 82322532

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD. (Hsinchu, TW)

Appl. No.: 18/329214

Filed: June 05, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230317795 A1	Oct. 05, 2023

Related U.S. Application Data

division parent-doc US 17207058 20210319 US 11670681 child-doc US 18329214

Publication Classification

Int. Cl.: H10D30/69 (20250101); H01L21/02 (20060101); H01L21/306 (20060101); H01L21/308 (20060101); H01L23/544 (20060101); H10D62/832 (20250101); H10D84/01 (20250101); H10D84/03 (20250101); H10D84/85 (20250101)

U.S. Cl.:

CPC H10D30/751 (20250101); H01L21/02532 (20130101); H01L21/30604 (20130101); H01L21/30625 (20130101); H01L21/308 (20130101); H01L23/544 (20130101); H10D62/832 (20250101); H10D84/0167 (20250101); H10D84/0188 (20250101); H10D84/0191 (20250101); H10D84/0193 (20250101); H10D84/038 (20250101); H10D84/853 (20250101); H10D84/859 (20250101); H01L2223/54426 (20130101)

Field of Classification Search

CPC: H01L (21/845); H01L (23/544)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5950093	12/1998	Wei	257/E21.549	H01L 21/76232
8772109	12/2013	Colinge	N/A	N/A
8785285	12/2013	Tsai et al.	N/A	N/A
8816444	12/2013	Wann et al.	N/A	N/A
8823065	12/2013	Wang et al.	N/A	N/A
8860148	12/2013	Hu et al.	N/A	N/A
9105490	12/2014	Wang et al.	N/A	N/A
9236267	12/2015	De et al.	N/A	N/A
9236300	12/2015	Liaw	N/A	N/A
9520482	12/2015	Chang et al.	N/A	N/A
9576814	12/2016	Wu et al.	N/A	N/A
10535654	12/2019	Tsai et al.	N/A	N/A
10535736	12/2019	More et al.	N/A	N/A
2011/0273685	12/2010	Li	355/53	G03B 27/54
2015/0115436	12/2014	Han et al.	N/A	N/A
2015/0243509	12/2014	Chan	438/424	H01L 21/3088
2016/0141252	12/2015	Wei	257/401	H10D 84/834
2016/0163810	12/2015	Huang et al.	N/A	N/A
2016/0308048	12/2015	Ching et al.	N/A	N/A
2017/0221709	12/2016	Jeno et al.	N/A	N/A
2017/0250183	12/2016	Brunco	N/A	N/A
2017/0352541	12/2016	Hsu et al.	N/A	N/A
2018/0025901	12/2017	Park et al.	N/A	N/A
2018/0061967	12/2017	Bi et al.	N/A	N/A
2018/0233522	12/2017	Liang	N/A	H01L 27/14614

2018/0301559	12/2017	Liaw	N/A	H01L 29/66795
2019/0096997	12/2018	More et al.	N/A	N/A
2019/0157159	12/2018	Wen et al.	N/A	N/A
2019/0326290	12/2018	Cea et al.	N/A	N/A
2019/0341403	12/2018	Wang et al.	N/A	N/A
2020/0058739	12/2019	Liaw	N/A	N/A
2022/0052042	12/2021	Lin et al.	N/A	N/A

Primary Examiner: Turner; Brian

Attorney, Agent or Firm: HAYNES AND BOONE, LLP

Background/Summary

PRIORITY (1) This is a divisional application of U.S. application Ser. No. 17/207,058, filed Mar. 19, 2021, which claims the benefits to U.S. Provisional Application No. 63/137,592, filed Jan. 14, 2021, each of which is incorporated herein by reference in its entirety.

BACKGROUND

(1) The electronics industry has experienced an ever-increasing demand for smaller and faster electronic devices that are simultaneously able to support a greater number of increasingly complex and sophisticated functions. To meet these demands, there is a continuing trend in the integrated circuit (IC) industry to manufacture low-cost, high-performance, and low-power ICs. Thus far, these goals have been achieved in large part by reducing IC dimensions (for example, minimum IC feature size), thereby improving production efficiency and lowering associated costs. However, such scaling has also increased complexity of the IC manufacturing processes. Thus, realizing continued advances in IC devices and their performance requires similar advances in IC manufacturing processes and technology.

(2) FinFET devices have been introduced to increase gate-channel coupling, reduce OFF-state current, and reduce short-channel effects (SCEs) over planar transistors. As the device downscaling continues, traditional FinFET also approaches its performance limitations. For example, aggressively-tight gate dimensions and tiny device volume make doping and strain engineering for performance very challenging for FinFET devices. Improvements for FinFET manufacturing is highly desired.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The present disclosure is best understood from the following detailed description when read with the accompanying figures. It is emphasized that, in accordance with the standard practice in the industry, various features are not drawn to scale and are used for illustration purposes only. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. 1A, 1B, and 1C show flow charts of a method of forming a semiconductor device, according to various aspects of the present disclosure.

(3) FIGS. 2, 3, 4, 5, 6, 6A, 7, 8, 9, 10, 11, 12, 13, 14, 14A, 14B, 15, 16, 17, 18, 19, 20, and 23 illustrate cross-sectional views of a portion of a semiconductor device, according to some embodiments, in intermediate steps of fabrication according to embodiments of the method of FIGS. 1A-1C.

(4) FIG. 17A illustrates a top view of a portion of a semiconductor device, according to some embodiments.

(5) FIGS. 21 and 22 illustrate perspective views of a portion of a semiconductor device, according to some embodiments.

DETAILED DESCRIPTION

(6) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. Still further, when a number or a range of numbers is described with “about,” “approximate,” and the like, the term encompasses numbers that are within certain variations (such as $\pm 10\%$ or other variations) of the number described, in accordance with the knowledge of the skilled in the art in view of the specific technology disclosed herein, unless otherwise specified. For example, the term “about 5 nm” may encompass the dimension range from 4.5 nm to 5.5 nm, 4.0 nm to 5.0 nm, etc.

(8) This application generally relates to semiconductor structures and fabrication processes, and more particularly to CMOS (complementary metal-oxide-semiconductor) devices with p-channel FinFET transistors and n-channel FinFET transistors. An object of the present disclosure is to provide methods of forming p-channel fins and n-channel fins on the same substrate where the n-channel fins include a first semiconductor material and the p-channel fins include a second semiconductor material that has a higher charge carrier (e.g., hole) mobility than the first semiconductor material. In an embodiment of the present disclosure, the first semiconductor material is crystalline silicon (Si) and the second semiconductor material is silicon germanium alloy (SiGe). In an embodiment, the p-channel fins are used for forming p-type FinFET and the n-channel fins are used for forming n-type FinFET. Using the p-channel fins further enhances the performance of the p-type FinFET over approaches where both n-type FinFET and p-type FinFET use the same material in their channels.

(9) Embodiments of the present disclosure also improve the epitaxial growth of the semiconductor materials for the p-channel fins by an isothermal process. For example, an embodiment of the present disclosure grows silicon germanium alloy by (a) performing an H.sub.2 baking process to a workpiece, (b) depositing a silicon seed layer on the workpiece, and (c) depositing a SiGe layer on the silicon seed layer, wherein the steps (a), (b), and (c) are performed under about the same temperature. In an example, the temperatures under which the steps (a), (b), and (c) are performed may vary by up to $\pm 10^\circ\text{C}$. In an embodiment, the steps (a), (b), and (c) are performed under a temperature that is in a range of about 650°C . to 750°C . The isothermal process simplifies the overall process because there is no need to ramp up and down the temperatures for the individual steps (a), (b), and (c), thereby reducing the fabrication time. Further, grown under the isothermal

process, the SiGe layer has improved quality and reduced defects across the whole wafer. For example, the SiGe layer has a substantially flat top surface and the thickness of the SiGe layer across a whole wafer is more uniform than it would have been when the H.sub.2 baking and the SiGe layer deposition are performed at different temperatures (for example, when the H.sub.2 baking is performed at 900° C. to 1000° C. and the SiGe layer deposition is performed at 650° C. to 750° C.). This is particularly beneficial when the wafer provides Si and SiGe fin channels for differently-sized devices such as SRAM (1 or 2 fins, small channel length devices), TCD (three fin devices), and IO (input/output, multi-fins large channel length devices). In other approaches, the thickness of a SiGe layer in differently-sized device regions have a large variation, such as 10 nm to 30 nm variation. With the method of the present disclosure, the thickness variation is reduced to less than 10 nm, such as less 8 nm, across the whole wafer. The uniform thickness improves the performance of subsequent processes such as chemical mechanical planarization (or polishing) (CMP). Those of ordinary skill in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein.

(10) FIGS. 1A, 1B, and 1C are a flow chart of a method **10** for fabricating a semiconductor device (or semiconductor structure) **100** according to various aspects of the present disclosure. Additional processing is contemplated by the present disclosure. Additional operations can be provided before, during, and after method **10**, and some of the operations described can be moved, replaced, or eliminated for additional embodiments of method **10**.

(11) Method **10** is described below in conjunction with FIG. 2 through FIG. 23 that illustrate various views of the semiconductor device **100** at various steps of fabrication according to the method **10**, in accordance with some embodiments. In some embodiments, the device **100** is a portion of an IC chip, a system on chip (SoC), or portion thereof, that includes various passive and active microelectronic devices such as resistors, capacitors, inductors, diodes, p-type field effect transistors (PFETs or pFETs), n-type field effect transistors (NFETs or nFETs), FinFET, nanosheet FETs, nanowire FETs, other types of multi-gate FETs, metal-oxide semiconductor field effect transistors (MOSFETs), complementary metal-oxide semiconductor (CMOS) transistors, bipolar junction transistors (BJTs), laterally diffused MOS (LDMOS) transistors, high voltage transistors, high frequency transistors, memory devices, other suitable components, or combinations thereof. FIGS. 2 through 23 have been simplified for the sake of clarity to better understand the inventive concepts of the present disclosure. Additional features can be added in the device **100**, and some of the features described below can be replaced, modified, or eliminated in other embodiments of the device **100**.

(12) At operation **12**, the method **10** (FIG. 1A) provides or is provided with a substrate **102**, such as shown in FIG. 2. In the depicted embodiment, the substrate **102** is a silicon substrate, such as a silicon wafer having crystalline silicon. Alternatively, the substrate **102** may comprise another elementary semiconductor, such as germanium; a compound semiconductor including silicon carbide, gallium nitride, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and indium antimonide; an alloy semiconductor including silicon germanium, gallium arsenide phosphide, aluminum indium phosphide, aluminum gallium arsenide, gallium indium arsenide, gallium indium phosphide, and gallium indium arsenide phosphide; or combinations thereof.

(13) At operation **14**, the method **10** (FIG. 1A) forms an alignment mark **110** in the substrate **102** (FIG. 5). This may involve multiple processes, such as illustrated in FIGS. 2-5. As shown in FIG. 2, a dielectric layer **104** is deposited over the substrate **102** and a dielectric layer **106** is deposited over the dielectric layer **104**. In an embodiment, the dielectric layer **104** includes an oxide (such as SiO.sub.2), and the dielectric layer **106** includes a nitride such as silicon nitride (Si.sub.3N.sub.4). As shown in FIG. 3, a trench **108** is etched into the dielectric layers **104**, **106**, and the substrate **102**. For example, the method **10** may form a resist pattern using a photolithography process that includes forming a resist layer over the device **100** (e.g., by spin coating), performing a pre-

exposure baking process, performing an exposure process using a photomask, performing a post-exposure baking process, and developing the exposed resist layer in a developer solution. Alternatively, the exposure process can be implemented or replaced by other methods, such as maskless lithography, e-beam writing, ion-beam writing, or combinations thereof. After development, the resist layer becomes a resist pattern that provides an opening corresponding to the trench **108**. Then, the dielectric layers **104**, **106**, and the substrate **102** are etched through the resist pattern to form the trench **108**. Thereafter, the resist pattern is removed, for example, using resist stripping. As shown in FIG. **4**, the dielectric layer **106** is removed, for example, using an etching process that is selective to the material of the dielectric layer **106**. As shown in FIG. **5**, a dielectric layer **110** is filled into the trench **108** and becomes an alignment mark **110**. In an embodiment, the dielectric layer **110** includes an oxide and may be the same as or substantially the same as the material in the dielectric layer **104**.

(14) At operation **16**, the method **10** (FIG. **1A**) forms N wells **116** and P wells **118** into the substrate **102** (FIG. **6**). This may involve multiple processes. For example, the method **10** may form an implant mask **112** over the dielectric layer **104** and the alignment mark **110**, such as shown in FIG. **5**. The implant mask **112** provides an opening **114** that corresponds to an area of the substrate **102** where an N well is to be formed. The implant mask **112** may be a resist pattern formed using a photolithography process as discussed above. In an embodiment, the alignment mark **110** is used to determine where the opening **114** is formed during the photolithography process. For example, the opening **114** is formed at certain distance away from the alignment mark **110**. Then, ion implantation may be used to form an n-type region (or N well) **116** in the substrate **102**. In some embodiments, the N well **116** is substantially aligned to the opening **114**. According to some embodiments, the n-type dopant may include arsenic (As), antimony (Sb), or phosphorous (P). According to some embodiments, the n-type dopant concentration in the N well **116** can range from about 5×10^{16} atoms/cm.³ to about 1×10^{19} atoms/cm.³. By way of example and not limitation, the N well **116** can have a depth (e.g., z-direction) of about 100 nm to about 500 nm. However, the width (e.g., along the x-direction) and length (e.g., along the y-direction, into the page of FIG. **5**) can vary depending on the device (e.g., logic, static random access memory (SRAM), etc.). After the formation of the N well **116**, the implant mask **112** can be removed.

(15) In an embodiment, a similar process that involves patterning a photoresist layer as an implant mask can be used to form a p-type region (P well) **118** in the substrate **102**, which is adjacent to the N well **116**, as shown in FIG. **6**. In some embodiments, the P well **118** can be created with an ion implantation process using a p-type dopant such as boron (B). By way of example and not limitation, the P well **118** can have a dopant concentration that ranges from about 5×10^{16} atoms/cm.³ to about 1×10^{19} atoms/cm.³. In some embodiments, an annealing step is performed to activate the dopants (e.g., move the dopants from interstitial sites to silicon lattice sites) in the N well **116** and the P well **118** and repair any silicon crystal damage which occurred during the ion implantation step. According to some embodiments, the dielectric layer **104** is removed after the dopant activation anneal, but the alignment mark **110** remains in the substrate **102**. For example, the dielectric layer **104** may be removed by chemical mechanical planarization (CMP) and/or etching processes.

(16) In some embodiment, the P well **118** is formed at a distance away from the alignment mark **110**, such as shown in FIG. **6**. In some embodiment, the P well **118** is formed such that the alignment mark **110** is within the P well **118**, such as shown in FIG. **6A**. In the following discussion of the method **10**, the embodiment depicted in FIG. **6** is used as an example. However, the same discussion can be applied to the embodiment depicted in FIG. **6A**.

(17) At operation **18**, the method **10** (FIG. **1A**) forms a semiconductor layer **120** over the N well **116**, the P well **118**, and the alignment mark **110**, such as shown in FIG. **7**. For example, a layer of silicon can be epitaxially grown directly on the substrate **102** as the semiconductor layer **120**. For example, silicon can be epitaxially grown with a chemical vapor deposition (CVD) process using

precursors such as silane (SiH.sub.4), silicon tetrachloride (SiCl.sub.4), trichlorosilane (TCS), or dichlorosilane (SiH.sub.2Cl.sub.2 or DCS). In some embodiments, the semiconductor layer **120** can have a thickness in a range between about 30 nm to about 100 nm.

(18) At operation **20**, the method **10** (FIG. **1A**) forms an alignment trench **122** in the semiconductor layer **120**. In an embodiment, the alignment trench **122** is formed overlapping with (for example, directly above) the alignment mark **110**, such as shown in FIG. **8**. Alternatively, the alignment trench **122** may be formed non-overlapping with the alignment mark **110**. As will be discussed, another alignment mark will be formed in the alignment trench **122**. The alignment trench **122** and the alignment mark therein can assist with the fabrication of fully strained channels in the semiconductor layer **120**. The alignment trench **122** may be formed using the same or similar way as the way the alignment trench **108** is formed, as discussed above (i.e., using photolithography and etching processes).

(19) At operation **22**, the method **10** (FIG. **1A**) deposits a dielectric layer **124** over the semiconductor layer **120** and in the alignment trench **122**, such as shown in FIG. **9**. For example, the dielectric layer **124** may include an oxide, such as silicon dioxide (SiO.sub.2). In the embodiment depicted in FIG. **9**, the dielectric layer **124** is deposited over the sidewall and the bottom surface of the alignment trench **122** but does not fully fill the alignment trench **122**. In an alternative embodiment, the dielectric layer **124** fully fills the alignment trench **122**.

(20) At operation **24**, the method **10** (FIG. **1A**) forms an etch mask layer **126** over the dielectric layer **124**. In an embodiment where the dielectric layer **124** partially fills the alignment trench **122**, the etch mask layer **126** fills into the remaining portion of the alignment trench **122**, such as shown in FIG. **10**. In an alternative embodiment where the dielectric layer **124** fully fills the alignment trench **122**, the etch mask layer **126** does not fill into the alignment trench **122** (not shown). The etch mask layer **126** may include a bottom anti-reflective coating (BARC) material in an embodiment.

(21) At operation **26**, the method **10** (FIG. **1A**) forms a resist pattern **128** over the etch mask layer **126**, such as shown in FIG. **11**. The resist pattern **128** provides an opening **130** that exposes an area of the etch mask layer **126** directly above the N well **116**. In an embodiment, the opening **130** is aligned with the N well **116** by using the alignment mark **110** and the alignment trench **122** (and the dielectric layers **124** therein). The resist pattern **128** may be formed using a photolithography process that includes spin coating a resist layer over the device **100**, baking the resist layer, exposing the resist layer using a photomask, performing post-exposure baking, and developing the exposed resist layer in a developer solution. Alternatively, the exposure process can be implemented or replaced by other methods, such as maskless lithography, e-beam writing, ion-beam writing, or combinations thereof. After development, the resist layer becomes the resist pattern **128**.

(22) At operation **28**, the method **10** (FIG. **1B**) etches the etch mask layer **126**, the dielectric layer **124**, and the semiconductor layer **120** through the opening **130** to form a trench **132** in the semiconductor layer **120**. The operation **28** may use one or more dry etching processes to etch the etch mask layer **126**, the dielectric layer **124**, and the semiconductor layer **120** such that the shape of the trench **132** substantially matches the opening **130**. In an embodiment, the semiconductor layer **120** is partially etched, leaving a thin portion **120a** of the semiconductor layer **120** at the bottom of the trench **132**, such as shown in FIG. **12**. This can be achieved by timing the dry etching processes. In an alternative embodiment, the semiconductor layer **120** is fully etched, thereby exposing the N well **116** in the trench **132** (not shown). In the embodiment depicted in FIG. **12**, the portion **120a** may have a thickness in a range about 0 nm to about 10 nm, such as from about 1 nm to about 5 nm. After the etching processes finish, the resist pattern **128** is removed, for example, using resist stripping, wet cleaning, or other suitable method.

(23) At operation **30**, the method **10** (FIG. **1B**) removes the etch mask layer **126**, for example, using cleaning, etching, or other suitable methods. In embodiments where the etch mask layer **126**

partially fills the trench **122**, the etch mask layer **126** is also removed from the trench **122**, such as shown in FIG. **13**. After the etch mask layer **126** is removed, the dielectric layer **124** still covers the semiconductor layer **120** except the surfaces of the semiconductor layer **120** exposed in the trench **132**. Then, the operation **30** may perform a cleaning process to the surfaces of the semiconductor layer **120** exposed in the trench **132**. For example, a cleaning process may apply plasma etching using a mixture of nitrogen trifluoride (NF.sub.3) and ammonia (NH.sub.3) gases. The plasma etching may also include inert gases such as argon (Ar), helium (He), hydrogen (H.sub.2), nitrogen (N.sub.2), or a combination thereof. The cleaning process may further include an anneal process. For example, the anneal process can be performed from about 30° C. to about 200° C. such as from about 60° C. to about 200° C. The cleaning process cleans the surfaces of the semiconductor layer **120** and make them ready for the subsequent epitaxial growth.

(24) At operation **32**, the method **10** (FIG. **1B**) epitaxially grows a semiconductor layer **134** in the trench **132**, such as shown in FIG. **14**. In an embodiment, the semiconductor layer **134** has a material that has a higher charge carrier (e.g., hole) mobility than the material of the semiconductor layer **120**. For example, the semiconductor layer **134** includes silicon germanium and the semiconductor layer **120** includes silicon. The semiconductor layer **134** provides strained channel material for p-type FinFETs. The semiconductor layer **134** is not grown on the surfaces of the dielectric layer **124**. In the present embodiment, the operation **32** includes three steps (or sub-operations): a baking step, a seed layer deposition step, and a main epitaxial growth step that forms an epitaxial layer on the seed layer. Further, the operation **32** is an isothermal operation. In other words, the operation **32** performs the three sub-operations at about the same temperature, taking into account any temperature variations caused by heating equipment or process chambers. For example, the temperature (recipe temperature) for the three sub-operations may be set to the same value in a process recipe but the temperatures (actual temperatures) under which the three sub-operations are actually performed may vary depending on the equipment used. In some embodiments, the actual temperatures may vary by up to $\pm 10^{\circ}$ C. throughout the three sub-operations. In some embodiments, the actual temperatures may vary by up to $\pm 5^{\circ}$ C. throughout the three sub-operations. In some embodiments, the actual temperatures may vary by up to $\pm 2\%$ of the recipe temperature throughout the three sub-operations. All these are considered to be within the meaning of the isothermal process of the present disclosure. In a further embodiment, the operation **32** is an isobaric process. In other words, the operation **32** performs the three sub-operations at about the same pressure, taking into account any pressure variations caused by process chambers. For example, the operation **32** may perform the three sub-operations at pressure of nominal 10 torr or another suitable pressure. In the present embodiment, the operation **32** epitaxially grows a silicon germanium layer **134** over a silicon seed layer **134a**. To further this embodiment, the three sub-operations (baking, Si seed layer deposition, and SiGe epitaxial growth) are performed at a temperature (recipe temperature) in a range from about 650° C. to about 750° C.

(25) The benefits of using an isothermal process in the operation **32** are many folds. For example, the operation **32** is more efficient than some approaches where different temperatures are used for different steps. Because the temperature is the same throughout the operation **32**, there is no need to ramp up and ramp down the temperatures in the process chamber(s), thereby reducing fabrication time. For example, if the baking step uses a higher temperature than the seed layer deposition step or the epitaxial growth step, then a cooling period would have to be included after the baking step, which would undesirably prolong the fabrication. Another benefit is that using an isothermal process improves the quality of the semiconductor layer **134**. This is further discussed with reference to FIG. **14B** which illustrates an enlarged cross-sectional view of the device **100**.

(26) Referring to FIG. **14**, in the present embodiment, the semiconductor layer **134** is grown such that its top surface is higher than the topmost surface of the semiconductor layer **120** but even with or lower than the topmost surface of the dielectric layer **124**. Due to the isothermal process, the top surface of the semiconductor layer **134** is substantially flat. In some experiments, the top surface of

the semiconductor layer **134** may vary about 10 nm or less, such as 8 nm or less or 5 nm or less, in different areas of a wafer, and in some cases the variation is only about 1 nm to about 2 nm across a whole wafer. In other words, the top surface of the semiconductor layer **134** may have a very high uniformity across a whole wafer in some embodiments. For example, the semiconductor layer **134** at different device regions on the same wafer (such as device regions for smaller transistors such as SRAM regions and device regions for larger transistors such as I/O regions or TCD regions) has a substantially uniform and coplanar top surface. This greatly reduces the difficulties in subsequent chemical mechanical planarization (CMP) processes, which will be discussed later. This also reduces the time for the CMP processes because there is less amount of material to be polished than approaches where the non-uniformity of the top surface of the semiconductor layer **134** is larger.

(27) In some embodiments, the edges of the dielectric layer **124** do not perfectly align with the trench **132** when the semiconductor layer **134** is grown. For example, this may occur during the process of cleaning the trench **132** where the cleaning plasma (such as NF.sub.3 and NH.sub.3) slightly etches the dielectric layer **124** (such as containing silicon dioxide). Thus, the top corners of the dielectric layer **124** may become rounded and the edges of the dielectric layer **124** may retreat from the edges of the trench **132**, such as shown in FIG. **14B**. In such embodiments, the semiconductor layer **134** may extend laterally over the semiconductor layer **120** by a width W. This portion of the semiconductor layer **134** is referred to as the extension portion **134b**. In some embodiments, the width W is in a range from about 5 nm to about 20 nm. The slope θ of the top surface of the extension portion **134b** (which is the angle between the top surface of the extension portion **134b** and the top surface of the semiconductor layer **120**) is in a range of 30 degrees or less, such as in a range of about 5 degrees to about 20 degrees in some embodiments. The slope θ is smaller than other approaches which do not use the disclosed isothermal process.

(28) In an embodiment, the baking step of the operation **32** is performed in H.sub.2 ambient at a pressure about 10 torr to about 600 torr and for about 30 seconds to about 120 seconds. Baking in H.sub.2 ambient controls reflow of the semiconductor layer **120**, reduces the surface roughness of the surfaces of the trench **132**, and removes oxide residue on the surfaces of the trench **132**, thereby improving the quality of subsequently deposited seed layer and epitaxial layer. In alternative embodiments, other gases may be additionally or alternatively used, such as argon (Ar), nitrogen (N.sub.2), helium (He), or a combination thereof. The baking step is performed at a temperature in a range from about 650° C. to about 750° C., which is the same temperature as the seed layer deposition and the epitaxial growth steps. This temperature is noticeably lower than other approaches. For example, some approaches may perform a baking process at a temperature ranging from 900° C. to 1000° C. and then perform the subsequent processes at a lower temperature (such as more than 20% lower). The lower thermal budget of the baking step as well as the isothermal process in the present disclosure result in the trench **132** having a better profile for epitaxial growth and contributes to the uniformity of the top surface of the semiconductor layer **134**, whose benefits have been discussed above.

(29) In an embodiment, the seed layer deposition step of the operation **32** may be performed at a pressure about 5 torr to about 50 torr, and the seed layer **134a** may be deposited to about 2 nm to about 10 nm thick on the surfaces of the trench **132**. In embodiments where the semiconductor layer **120** is partially etched when forming the trench **132**, the seed layer **134a** is deposited on the surfaces of the semiconductor layer **120** exposed in the bottom and sidewalls of the trench **132**, such as shown in FIG. **14**. In embodiments where the semiconductor layer **120** is fully etched when forming the trench **132**, the seed layer **134a** is deposited on the surface of the semiconductor layer **116** on the bottom of the trench **132** and on the surfaces of the semiconductor layer **120** exposed in the sidewalls of the trench **132**, such as shown in FIG. **14A**. In some embodiments, the seed layer **134a** may be deposited for about 3 seconds to about 10 seconds depending on the seed layer deposition rate and the desired seed layer thickness. The seed layer **134a** can be used to control the corner rounding of the semiconductor layer **134**. In some embodiments, the seed layer **134a** may be

a Si layer, a Si:C layer, a SiGe layer, or a combination thereof. For example, the seed layer **134a** can be Si/Si:C/SiGe, Si/SiGe, or Si:C/SiGe in some embodiments. According to some embodiments, the atomic percentage (at. %) of carbon dopant in Si:C can be from about 0.01 at. % to about 2 at. %. The seed layer **134a** can be deposited by CVD or other suitable methods (such as ALD). For example, a Si seed layer **134a** can be deposited using precursor gases SiH₄ and/or DCS and carrier gases H₂ or N₂. For another example, a SiGe seed layer **134a** can be deposited using precursor gases SiH₄, disilane (Si₂H₆), germane (GeH₄), and hydrochloric acid (HCl) and carrier gases H₂, N₂, He or Ar.

(30) In the main epitaxial growth step of the operation **32**, an epitaxial layer **134** is formed on the seed layer **134a** to fill the trench **132**. In an embodiment, the epitaxial layer **134** includes SiGe and can be grown using precursor gases such as SiH₄, Si₂H₆, SiH₂Cl₂, GeH₄, and/or HCl with a carrier gas such as H₂, N₂, Ar, or a combination thereof. Epitaxially growing SiGe can be performed at a pressure about 5 torr to about 50 torr. The epitaxial growth may be performed for about 80 seconds to about 200 seconds depending on the epitaxial growth rate and the depth of the trench **132**. In an embodiment, growth of the epitaxial layer **134** is controlled (e.g., timed) such that the top surface of the epitaxial layer **134** is above the top surface of the semiconductor layer **120** but even with or below the top surface of the dielectric layer **124**. In some embodiments, the Ge concentration in atomic percentage (at. %) is constant throughout the thickness (e.g., along the z-direction) of the SiGe epitaxial layer **134** and can range from about 20 at. % to about 40 at. %. In some embodiments, the SiGe epitaxial layer **134** may include a first sub-layer that has a Ge concentration up to about 5 at. %, and a second sub-layer with a constant Ge concentration throughout the thickness of the SiGe epitaxial layer ranging from about 20 at. % to about 40 at. %.

(31) At operation **34**, the method **10** (FIG. **1B**) deposits another dielectric layer **136** over the dielectric layer **124** and the semiconductor layer **134**, such as shown in FIG. **15**. In an embodiment, the dielectric layer **136** includes an oxide such as silicon dioxide. In an embodiment, both dielectric layers **124** and **136** include oxide such as silicon dioxide. Having the dielectric layer **136** assists in removing the dielectric layer **124** by a CMP process. Otherwise, since the dielectric layer **124** is relatively thin (for example, it may be about 10 nm to about 15 nm thick in some embodiments), it may not be easily removed by a CMP process without damaging the semiconductor layers **120** and **134**. The dielectric layer **136** may be deposited using CVD or other suitable processes. The dielectric layer **136** may be deposited to a thickness in a range from about 5 nm to about 20 nm in some embodiments. In the embodiment depicted in FIG. **15**, since the dielectric layer **124** does not fully fill the trench **122**, the dielectric layer **136** is deposited to fill the remaining portion of the trench **122**.

(32) At operation **36**, the method **10** (FIG. **1B**) performs a CMP process to remove the dielectric layers **136** and **124** from the device **100**, such as shown in FIG. **16**. In an embodiment, the CMP process is designed selective to the materials of the dielectric layers **136** and **124**. For example, the CMP process may use a slurry that is selective to the materials of the dielectric layers **136** and **124** but not to the materials of the semiconductor layers **134** and **120**. In the present embodiment, because the top surface of the semiconductor layer **134** is substantially flat and does not protrude above the dielectric layer **124**, the dielectric layers **136** and **124** can be removed by the CMP process completely from the surface of the semiconductor layer **120** with no dielectric residue on the surface of the semiconductor layer **120**. In some embodiments, the CMP process may leave negligible dielectric residue on the surface of the semiconductor layer **120**. As discussed above, in approaches that do not use the isothermal process of the present disclosure, the top surface of the semiconductor layer **134** may protrude above the dielectric layer **124** and may have a relatively large non-uniformity in different device regions of a wafer. Consequently, there may be a large amount of dielectric residue (such as 1 nm or 2 nm thick) on some areas of the top surface of the semiconductor layers **134** and **120** after a CMP process has been performed to remove the dielectric

layers **136** and **124**. Such large amount of dielectric residue may cause defects or defective devices in subsequent fabrication process. In contrast, in the present disclosure, the dielectric layers **136** and **124** can be completely removed from the top surfaces of the semiconductor layers **134** and **120**, and any dielectric residue on the top surfaces of the semiconductor layers **134** and **120** is negligible (for example, dielectric residue, if any, is less than about 0.5 nm to about 0.9 nm in some cases). As depicted in FIG. **16**, portions of the dielectric layers **136** and **124** remain in the trench **122** after the CMP process, thereby forming a dielectric alignment mark **138** in the semiconductor layer **120**. In some embodiments, when the dielectric layer **124** fully fills the trench **122** in the operation **22**, the alignment mark **138** includes only the dielectric layer **124** and not the dielectric layer **136**. This alignment mark **138** can be used to align the fins made from the semiconductor layers **134** and **120**. In the present embodiment, the alignment marks **138** and **110** may be considered different portions of a large alignment mark.

(33) At operation **38**, the method **10** (FIG. **1B**) performs another CMP process to the semiconductor layers **134** and **120** and the alignment mark **138**. In an embodiment, the CMP process is designed to be non-selective to the materials of the alignment mark **138** and the semiconductor layers **134** and **120**. In other words, the CMP process polishes the semiconductor layers **134** and **120** and the alignment mark **138** at about the same rate. As shown in FIG. **17**, after the CMP process finishes, the top surfaces of the semiconductor layers **134** and **120** and the alignment mark **138** are coplanar or substantially coplanar (up to the capability of the CMP process). In the present embodiment, because there is little to no dielectric residue on the semiconductor layers **134** and **120**, an extra etching for removing such dielectric residue is not needed. In some approaches where an etching process is applied after the CMP process to remove dielectric residue from the top surface of the semiconductor layer **120**, the alignment mark **138** would be recessed and its top surface would be lower than the top surface of the semiconductor layers **120** and **134**, unlike the present embodiment. When the alignment mark **138** is too low, it may not serve well as an alignment mark during subsequent photolithography processes. Because the top surfaces of the semiconductor layers **134** and **120** and the alignment mark **138** are coplanar or substantially coplanar, the alignment mark **138** is easily recognizable by metrology tools and serves well as an alignment mark during subsequent photolithography processes. In an embodiment, the CMP process may remove about 5 nm to about 15 nm of the respective materials along the “Z” direction. FIG. **17A** illustrates a portion of the device **100** at this fabrication stage from a top view. Referring to FIG. **17A**, the device **100** includes various pFET and nFET regions that are alternatively arranged along the “X” direction, which is the widthwise direction of fins to be fabricated later. The semiconductor layer **134** is provided in each of the pFET regions and the semiconductor layer **120** is provided in each of the nFET regions. The semiconductor layers **134** and **120** are oriented lengthwise along the “Y” direction, which is the lengthwise direction of fins to be fabricated later. The semiconductor layer **134** includes SiGe and the semiconductor layer **120** includes Si in this embodiment. In an embodiment, the semiconductor layer **120** in each of the nFET regions may be replaced with another semiconductor material using a method that is similar to the method of forming the semiconductor layer **134**.

(34) At operation **40**, the method **10** (FIG. **1C**) deposits a buffer semiconductor layer **150** over the planarized surfaces of the semiconductor layer **134**, the semiconductor layer **120**, and the alignment mark **138**, such as shown in FIG. **18**. In an embodiment, the buffer semiconductor layer **150** includes silicon, such as amorphous silicon. In some embodiments, the thickness of the buffer semiconductor layer **150** can range from about 1 nm to about 10 nm and can be epitaxially grown. The operation **40** may further clean various surfaces of the device **100**. For example, the operation **40** may perform SC1 (Standard Clean 1) cleaning to trim the buffer semiconductor layer **150**, apply diluted HF solution to the front and backside of the wafer as well as the edges of the wafer (bevel cleaning), and so on.

(35) At operation **42**, the method **10** (FIG. **1C**) forms hard mask layers **151** and **153** on the device

100, such as shown in FIG. **19**. In an embodiment, the hard mask layer **151** includes an oxide, such as silicon oxide (SiO_2), and the hard mask layer **153** includes a nitride, such as silicon nitride (Si_3N_4). In an embodiment such as depicted in FIG. **19**, the hard mask layer **151** has a step profile where it is higher on the semiconductor layer **134** than on the semiconductor layer **120**. (36) At operation **44**, the method **10** (FIG. **1C**) forms semiconductor fins **144** in the pFET regions and semiconductor fins **146** in the nFET regions, such as shown in FIGS. **20** and **21**. FIG. **21** shows a perspective view of the device **100**, in portion, at this fabrication stage. The operation **44** may involve a variety of processes. For example, the operation **44** may form an etch mask over the hard mask layer **153**. The etch mask may be formed using one or more photolithography processes, including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over the pad silicon nitride layer and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers, or mandrels, may then be used as the etch mask for patterning the fins **144** and **146**. For example, the operation **44** may etch the semiconductor layers **134**, **120** and the wells **116**, **118** using the etch mask as a masking element, leaving the fins **144** and **146** on the substrate **102**.

(37) After the fins **144** and **146** are formed, the operation **44** further forms an isolation structure **143** to electrically isolate the bottom portions of the fins **144** and **146**. The isolation structure **143** may include silicon oxide (SiO_2), silicon nitride (Si_3N_4), silicon oxynitride (SiON), fluoride-doped silicate glass (FSG), a low-k dielectric material, and/or other suitable insulating material. In an embodiment, the isolation structure **143** includes a dielectric liner **142** (such as thermal oxide) on the surfaces of the fins and the surfaces of the substrate **102** and a dielectric layer **140** (such as silicon nitride and/or silicon oxide) on the dielectric liner **142**. In an embodiment, the isolation structure **143** is formed by filling the trenches between fins **144** and **146** with one or more insulator materials (for example, by using a CVD process or a spin-on glass process); performing a chemical mechanical polishing (CMP) process to remove excessive insulator materials, and etching back the insulator materials to form the isolation structure **143**.

(38) As shown in FIG. **20**, each fin **144** includes a portion of the semiconductor layer **134** over the seed layer **134a** over the portion **120a** of the semiconductor layer **120** over a portion of the N well **116**; and each fin **146** includes a portion of the semiconductor layer **120** over a portion of the P well **118**. The semiconductor layers **134**, **134a**, **120a**, and **120** protrude above the isolation structure **143**. Further, the alignment mark **138** is above the isolation structure **143**. The top surfaces of the fins **144**, **146**, and the alignment mark **138** are substantially coplanar. The channel layers for p-type FinFET include the semiconductor layers **134** of the fins **144**. The channel layers for n-type FinFET include the semiconductor layers **120** of the fins **146**. Thus, the fins **144** and **146** are also referred to as pFET fins and nFET fins, respectively.

(39) At operation **46**, the method **10** (FIG. **1C**) proceeds to further fabrication steps to form FinFET devices over the pFET fins **144** and nFET fins **146**. For example, the operation **46** may form dummy gates over the fins **144** and **146**, form source/drain regions by etching the fins **144** and **146** in the source/drain regions and epitaxially growing source/drain features over remaining portions of the fins **144** and **146** in the source/drain regions, replace the dummy gates with high-k metal gates, form inter-layer dielectric layer, form contacts to the source/drain features and high-k metal gates, form multi-level interconnect structures, and perform other fabrications. In that regard, FIG. **22** illustrates a perspective view of the device **100** after the operation **46** forms FinFET, and FIG. **23** illustrates a cross-sectional view of the device **100** along the “B-B” line in FIG. **22**. As illustrated in FIGS. **22** and **23**, the operation **46** forms n-type FinFET over the nFET fins **146** and p-type FinFET over the pFET fins **144**, where portions of the fins **146** and **144** function as the channels for the

respective FinFET. In the embodiment shown in FIGS. 22 and 23, a common high-k metal gate 152 engages the fins 146 and 144 to form a CMOS device. In alternative embodiments, the n-type FinFET and the p-type FinFET may have separate high-k metal gates.

(40) Referring to FIGS. 22 and 23, in this embodiment, the device 100 includes a high-k metal gate 152, gate spacers 154 on sidewalls of the high-k metal gate 152, fin sidewall spacers 156, n-type source/drain features 158_n over a remaining portion of the fin 146 (after a source/drain trench etching process), and p-type source/drain features 158_p over a remaining portion of the fin 144 (after a source/drain trench etching process). The device 100 may include various other elements not shown in FIGS. 22 and 23. Referring to FIG. 23, in the p-type FinFET, the high-k metal gate 152 is disposed over the top portion 134 of the pFET fin 144 which provides high charge carrier mobility. The top portion 134 of the pFET fin 144 connects the two p-type source/drain features 158_p and functions as the transistor channel. Because the top portion 134 uses a high-mobility semiconductor material such as SiGe, the performance of the p-type FinFET is improved. In the present embodiment, the top portion 134 of the pFET fins 144 is partially etched in the source/drain regions and the source/drain features 158_p are disposed directly on remaining portions of the top portion 134 in the source/drain region. In an alternative embodiment, the top portion 134 of the pFET fins 144 is fully etched in the source/drain regions and the source/drain features 158_p are disposed directly on the bottom portion 120_a or 116 in the source/drain region.

(41) The source/drain features 158_n and 158_p may be formed by any suitable epitaxy process, such as vapor phase epitaxy, molecular beam epitaxy, other suitable epitaxial growth processes, or combinations thereof. In some embodiments, the source/drain features 158_n include silicon and can be doped with carbon, phosphorous, arsenic, other n-type dopant, or combinations thereof (for example, forming Si:C epitaxial source/drain features, Si:P epitaxial source/drain features, or Si:C:P epitaxial source/drain features). In some embodiments, the source/drain features 158_p include silicon germanium or germanium and can be doped with boron, other p-type dopant, or combinations thereof (for example, forming Si:Ge:B epitaxial source/drain features). In some embodiments, epitaxial source/drain features 158_n and 158_p are doped during deposition by adding impurities to a source material of the epitaxy process (i.e., in-situ). In some embodiments, epitaxial source/drain features 158_n and 158_p are doped by an ion implantation process subsequent to a deposition process. In some embodiments, annealing processes (e.g., rapid thermal annealing (RTA) and/or laser annealing) are performed to activate dopants in the epitaxial source/drain features 158_n and 158_p. In some embodiments, epitaxial source/drain features 158_n and 158_p are formed in separate processing sequences that include, for example, masking pFET regions when forming epitaxial source/drain features 158_n in nFET regions and masking nFET regions when forming epitaxial source/drain features 158_p in pFET regions.

(42) In an embodiment, the high-k metal gate 152 includes a high-k gate dielectric layer 152A and a gate electrode layer 152B. The gate electrode layer 152B may include a work function layer and a bulk metal layer. The high-k metal gate 152 may include additional layers such as a dielectric interfacial layer between the top portion 134 and the high-k gate dielectric layer 152A. In various embodiments, the dielectric interfacial layer may include a dielectric material such as silicon oxide, silicon oxynitride, or silicon germanium oxide, and may be formed by chemical oxidation, thermal oxidation, atomic layer deposition (ALD), chemical vapor deposition (CVD), and/or other suitable methods. The dielectric interfacial layer may include different dielectric materials for n-type FinFET and for p-type FinFET. For example, the dielectric interfacial layer may include silicon oxide for n-type FinFET and silicon germanium oxide for p-type FinFET. The high-k gate dielectric layer 152A may include hafnium oxide (HfO₂), zirconium oxide (ZrO₂), lanthanum oxide (La₂O₃), titanium oxide (TiO₂), yttrium oxide (Y₂O₃), strontium titanate (SrTiO₃), other suitable metal-oxides, or combinations thereof; and may be formed by ALD and/or other suitable methods. The work function layer (part of the gate electrode layer 152B) may include a metal selected from but not restricted to the group of titanium aluminum

nitride (TiAlN), titanium nitride (TiN), tantalum nitride (TaN), ruthenium (Ru), molybdenum (Mo), tungsten (W), platinum (Pt), aluminum (Al), or combinations thereof; and may be deposited by CVD, PVD, and/or other suitable process. The bulk metal layer (part of the gate electrode layer **152B**) may include a metal such as aluminum (Al), tungsten (W), cobalt (Co), copper (Cu), and/or other suitable materials; and may be deposited using plating, CVD, PVD, or other suitable processes.

(43) Each of the fin sidewall spacers **156** and the gate spacers **154** may be a single layer or multi-layer structure. In some embodiments, each of the spacers **156** and **154** includes a dielectric material, such as silicon oxide (SiO₂), silicon nitride (Si₃N₄), silicon oxynitride (SiON), other dielectric material, or combination thereof. In an example, the spacers **156** and **154** are formed by depositing a first dielectric layer (e.g., a SiO₂ layer having a substantially uniform thickness) as a liner layer over the device **100**, and a second dielectric layer (e.g., a Si₃N₄ layer) as a main D-shaped spacer over the first dielectric layer, and then, anisotropically etching to remove portions of the dielectric layers to form the spacers **156** and **154**. Additionally, the fin sidewall spacers **156** may be partially removed during the etching process that forms recesses into the fins **146** and **144** prior to growing the source/drain features **158n** and **158p**. In some embodiments, the fin sidewall spacers **156** may be completely removed by such etching process.

(44) Although not intended to be limiting, embodiments of the present disclosure provide one or more of the following advantages. For example, embodiments of the present disclosure form pFET fins and nFET fins over the same substrate where the pFET fins include a channel semiconductor material that has higher hole mobility than the channel semiconductor material in the nFET fins. This improves the performance of p-type FinFET formed from the pFET fins. Further, growth of the channel semiconductor material for the pFET fins uses an isothermal process which not only reduces fabrication time but also improves the quality of the channel semiconductor material. Embodiments of the present disclosure can be readily integrated into existing semiconductor manufacturing processes.

(45) In one example aspect, the present disclosure is directed to a method. The method includes forming an N well and a P well in a substrate; depositing a first layer having silicon over the N well and the P well; depositing a first dielectric layer over the first layer; forming a resist pattern over the first dielectric layer, the resist pattern providing an opening directly above the N well; etching the first dielectric layer and the first layer through the opening, leaving a first portion of the first layer over the N well; removing the resist pattern; and epitaxially growing a second layer having silicon germanium (SiGe) over the first portion of the first layer. The epitaxially growing the second layer includes steps of (a) performing a baking process, (b) depositing a silicon seed layer, and (c) depositing a SiGe layer over the silicon seed layer, wherein the steps (a), (b), and (c) are performed under about a same temperature.

(46) In an embodiment of the method, the steps (a), (b), and (c) are performed under a temperature in a range of about 650° C. to 750° C. In another embodiment, the baking process is performed in H₂ ambient.

(47) In an embodiment, the method further includes depositing a second dielectric layer over the first dielectric layer and over the SiGe layer; performing a first chemical mechanical polishing (CMP) process to the second dielectric layer and the first dielectric layer; and performing a second CMP process to the SiGe layer and the first layer. In a further embodiment, the method includes patterning the first layer and the P well to form first fins; patterning the SiGe layer and the N well to form second fins; and forming an isolation feature to isolate bottom portions of the first fins and the second fins. In a further embodiment, the method includes forming n-type FinFET over the first fins and above the isolation feature; and forming p-type FinFET over the second fins and above the isolation feature.

(48) In an embodiment, before the depositing of the first layer, the method further includes forming

a portion of an alignment mark into the substrate. In another embodiment, before the depositing of the first dielectric layer, the method further includes forming an alignment trench into the first layer.

(49) In an embodiment of the method, the second layer is epitaxially grown such that its top surface is higher than a top surface of the first layer and is lower than a top surface of the first dielectric layer. In another embodiment, temperatures under which the steps (a), (b), and (c) are performed vary less than $\pm 10^{\circ}\text{C}$.

(50) In another example aspect, the present disclosure is directed to a method. The method includes providing a substrate; depositing a silicon layer over the substrate; etching an alignment trench into the silicon layer; depositing a first oxide layer over the silicon layer and in the alignment trench; forming an etch mask over the first oxide layer, wherein the etch mask covers the alignment trench and has an opening directly above a first portion of the silicon layer; etching the first oxide layer and the first portion of the silicon layer through the opening, thereby forming a first trench; removing the etch mask; and epitaxially growing a second layer having silicon germanium (SiGe) in the first trench, wherein the epitaxially growing the second layer includes steps of (a) performing a baking process, (b) depositing a silicon seed layer, and (c) depositing a SiGe layer on the silicon seed layer, wherein the steps (a), (b), and (c) are performed under about a same temperature.

(51) In an embodiment, the method further includes depositing a second oxide layer over the first oxide layer and over the SiGe layer; performing a first chemical mechanical polishing (CMP) process to the first and the second oxide layers; and performing a second CMP process to the SiGe layer.

(52) In an embodiment of the method, the steps (a), (b), and (c) are performed under a temperature in a range of about 650°C . to 750°C . In another embodiment, the second layer is epitaxially grown such that its top surface is higher than a top surface of the silicon layer and is about even with or lower than a top surface of the first oxide layer.

(53) In some embodiment, the baking process is performed in H.sub.2 ambient. In some embodiment, the baking process is performed in ambient having N.sub.2 , Ar, He, or a combination thereof. In an embodiment, the etching of the first portion of the silicon layer through the opening leaves a layer of the first portion of the silicon layer in the first trench.

(54) In yet another example aspect, the present disclosure is directed to a semiconductor structure that includes a substrate, a first fin extending from the substrate, and an alignment mark over the substrate and having one or more dielectric layers. The first fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion include different materials, and the upper portion includes silicon germanium. A top surface of the first fin is substantially coplanar with a top surface of the alignment mark.

(55) In an embodiment, the alignment mark partially extends into the substrate. In another embodiment, the alignment mark includes a first dielectric layer and a second dielectric layer over the first dielectric layer.

(56) The foregoing outlines features of several embodiments so that those of ordinary skill in the art may better understand the aspects of the present disclosure. Those of ordinary skill in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those of ordinary skill in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor structure, comprising: a substrate; a first fin extending from the substrate, wherein the first fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion include different materials, and the upper portion includes silicon germanium; and an alignment mark over the substrate and having one or more dielectric layers extending above a top surface of the substrate, wherein a top surface of the first fin is substantially coplanar with a top surface of the one or more dielectric layers, wherein the bottom portion of the first fin is an N well portion of the substrate, and a bottom surface of the N well portion is substantially coplanar with a bottom surface of the alignment mark.
2. The semiconductor structure of claim 1, wherein the alignment mark partially extends into the substrate.
3. The semiconductor structure of claim 1, wherein the alignment mark includes a bottom portion and a top portion over the bottom portion, the bottom portion having a first dielectric layer and the top portion having a second dielectric layer over the first dielectric layer.
4. The semiconductor structure of claim 3, wherein the first dielectric layer has a top surface substantially coplanar with a top surface of the substrate.
5. The semiconductor structure of claim 1, wherein a bottom portion of the alignment mark is embedded in a P well portion of the substrate.
6. The semiconductor structure of claim 5, wherein the first fin further includes a silicon seed layer between the bottom portion and the upper portion of the first fin.
7. The semiconductor structure of claim 1, further comprising a second fin extending from the substrate, wherein the second fin includes a bottom portion and an upper portion over the bottom portion, the bottom portion and the upper portion of the second fin include silicon.
8. The semiconductor structure of claim 7, wherein the bottom portion of the second fin is a P well portion of the substrate.
9. The semiconductor structure of claim 1, further comprising an isolation structure over the substrate, the isolation structure surrounds the bottom portion of the first fin.
10. A semiconductor structure, comprising: a substrate; a first fin extending from the substrate, wherein the first fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion include different semiconductor materials, and the upper portion includes silicon germanium; an isolation structure over the substrate, wherein a top surface of the isolation structure is substantially coplanar with a top surface of the bottom portion of the first fin; and an alignment mark over the substrate, the alignment mark having a bottom portion and a top portion, the bottom portion of the alignment mark is adjacent to the isolation structure, and the top portion of the alignment mark extends above the top surface of the isolation structure, wherein the top portion of the alignment mark spans a greater lateral width than the bottom portion of the alignment mark, and the top portion of the alignment mark is laterally surrounded by a semiconductor material different from that of the upper portion of the first fin.
11. The semiconductor structure of claim 10, wherein the bottom portion of the alignment mark includes silicon oxide, wherein the top portion of the alignment mark includes silicon oxide and a bottom anti-reflective coating (BARC) material.
12. The semiconductor structure of claim 10, wherein the bottom portion of the first fin is doped with an n-type dopant and the upper portion of the first fin is free of the n-type dopant.
13. The semiconductor structure of claim 10, further comprising: a second fin extending from the substrate, wherein the second fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion of the second fin include silicon, wherein the bottom portion of the second fin is doped with a p-type dopant and the upper portion of the second fin is free of the p-type dopant.
14. The semiconductor structure of claim 13, further comprising: n-type source/drain features directly on the upper portion of the first fin; and p-type source/drain features directly on the upper

portion of the second fin.

15. The semiconductor structure of claim 13, wherein the top surface of the isolation structure is substantially coplanar with a top surface of the bottom portion of the second fin.

16. The semiconductor structure of claim 10, wherein the bottom portion and the top portion of the alignment mark both includes silicon oxide.

17. A semiconductor structure, comprising: a substrate; a first fin extending from the substrate, wherein the first fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion of the first fin include different material compositions, and the upper portion of the first fin includes silicon germanium, wherein a silicon seed layer is disposed between the bottom portion and the upper portion of the first fin; and a second fin extending from the substrate, wherein the second fin includes a bottom portion and an upper portion over the bottom portion, the upper portion and the bottom portion of the second fin include different material compositions, and the upper portion of the second fin includes silicon; an isolation structure between the bottom portions of the first fin and the second fin; and an alignment mark having one or more dielectric layers over the substrate and above the isolation structure, wherein the one or more dielectric layers spans from below a bottom surface of the isolation structure to a top surface of the first and second fins, wherein a top portion of the alignment mark spans a greater lateral width than the bottom portion of the alignment mark, and the top portion of the alignment mark is laterally surrounded by a same semiconductor material as the silicon seed layer, wherein the bottom portion of the first fin includes n-type dopants, and the upper portion of the first fin is free of the n-type dopants, and a bottom surface of the bottom portion of the first fin is substantially coplanar with a bottom surface of the alignment mark.

18. The semiconductor structure of claim 17, wherein the bottom portion of the second fin includes p-type dopants, and the upper portion of the second fin is free of the p-type dopants.

19. The semiconductor structure of claim 18, wherein the isolation structure surrounds the bottom portions of the first and second fins.

20. The semiconductor structure of claim 17, wherein top surfaces of the first and second fins are substantially coplanar with a top surface of the alignment mark.
