

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250281371

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

OUALI; Lahoussine et al.

PLANT PROTEIN-BASED MICROCAPSULES

Abstract

Described herein is a process for the preparation of plant protein-based microcapsules. Also described herein are protein-based microcapsules and perfuming compositions and consumer products including the microcapsules, in particular perfumed consumer products in the form of home care or personal care products.

Inventors: OUALI; Lahoussine (Satigny, CH), NICOLAE; Anaick (Satigny, CH), JACQUEMOND; Marlène (Satigny, CH), ETCHENAUSIA; Laura (Satigny, CH), VALMACCO; Valentina (Satigny, CH)

Applicant: Firmenich SA (Satigny, CH)

Family ID: 1000008672364

Appl. No.: 18/293863

Filed (or PCT Filed): September 27, 2022

PCT No.: PCT/EP22/76819

Foreign Application Priority Data

EP	21200666.2	Oct. 04, 2021
EP	21205885.3	Nov. 02, 2021

Publication Classification

Int. Cl.: A61K8/11 (20060101); A61K8/64 (20060101)

U.S. Cl.:

CPC A61K8/11 (20130101); A61K8/645 (20130101); A61K2800/412 (20130101)

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates to a new process for the preparation of plant protein-based microcapsules. Plant protein-based microcapsules are also an object of the invention. Perfuming compositions and consumer products comprising said microcapsules, in particular perfumed consumer products in the form of home care or personal care products, are also part of the invention.

BACKGROUND OF THE INVENTION

[0002] One of the problems faced by the perfumery industry lies in the relatively rapid loss of olfactive benefit provided by odoriferous compounds due to their volatility, particularly that of “top-notes”. In order to tailor the release rates of volatiles, delivery systems such as microcapsules containing a perfume are needed to protect and later release the core payload when triggered. A key requirement from the industry regarding these systems is to survive suspension in challenging bases without physically dissociating or degrading. This is referred to as stability for the delivery system. For instance, fragranced personal and household cleansers containing high levels of aggressive surfactant detergents are very challenging for the stability of microcapsules.

[0003] Polyurea and polyurethane-based microcapsule slurry are widely used for example in perfumery industry for instance as they provide a long lasting pleasant olfactory effect after their applications on different substrates. Those microcapsules have been widely disclosed in the prior art (see for example WO2007/004166 or EP 2300146).

[0004] In addition to the performance in terms of stability and olfactive performance, the consumer demand for eco-friendly delivery systems is more and more important and is driving the development of new delivery systems.

[0005] There is therefore still a need to provide new microcapsules using more eco-friendly materials, while not compromising on the performance of the microcapsules, in particular in terms of stability in a challenging medium such as a consumer product base, as well as in delivering a good performance in terms of active ingredient delivery, e.g. olfactive performance in the case of perfuming ingredients.

[0006] The present invention is proposing a solution to the above-mentioned problem by providing new plant protein-based microcapsules and a process for preparing said microcapsules.

SUMMARY OF THE INVENTION

[0007] It has now been found that performing core-shell microcapsules encapsulating hydrophobic material could be obtained by reacting a polyfunctional monomer (for example an acyl chloride) with optionally a reactant (for example at least one amino-compound) in the presence of a plant-based protein. The microcapsules of the invention therefore provide a solution to the above-mentioned problems as it allows preparing eco-friendly microcapsules with the desired stability in challenging bases.

[0008] In a first aspect, the present invention relates to a core-shell microcapsule comprising:

[0009] a core comprising a hydrophobic material, preferably a perfume oil, and [0010] a polymeric shell comprising a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof.

[0011] Another object of the invention is a core-shell microcapsule slurry comprising at least one microcapsule, the microcapsule comprising: [0012] a core comprising a hydrophobic material, preferably a perfume oil, and [0013] a polymeric shell comprising a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof.

[0014] Another object of the invention is a process for preparing a core-shell microcapsule slurry comprising the steps of: [0015] a) Preparing an oil phase comprising a hydrophobic material, preferably a perfume to form an oil phase; [0016] b) Dispersing the oil phase obtained in step a) into a water phase to form an oil-in water emulsion; [0017] c) Performing a curing step to form microcapsules in the form of a slurry; [0018] wherein a polyfunctional monomer is added in the oil phase and/or in the water phase, and [0019] wherein a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase.

[0020] The present invention also relates to perfumed consumer products and flavoured edible products comprising the microcapsules defined above.

Description

DETAILED DESCRIPTION OF THE INVENTION

[0021] Unless stated otherwise, percentages (%) are meant to designate a percentage by weight of a composition.

[0022] By “active ingredient”, it is meant a single compound or a combination of ingredients. By “perfume or flavour oil”, it is meant a single perfuming or flavouring compound or a mixture of several perfuming or flavouring compounds.

[0023] By “consumer product” or “end-product” it is meant a manufactured product ready to be distributed, sold and used by a consumer.

[0024] For the sake of clarity, by the expression “dispersion” in the present invention it is meant a system in which particles are dispersed in a continuous phase of a different composition and it specifically includes a suspension or an emulsion.

[0025] A “microcapsule”, or the similar, in the present invention it is meant that core-shell microcapsules have a particle size distribution in the micron range (e.g. a mean diameter ($d(v, 0.5)$) comprised between about 1 and 3000 microns, preferably between 1 and 500 microns) and comprise an external solid polymeric shell and an internal continuous oil phase enclosed by the external shell. According to a particular embodiment, the polymeric shell is a polyamide-based shell.

[0026] By “microcapsule slurry”, it is meant microcapsule(s) that is (are) dispersed in a liquid. According to an embodiment, the slurry is an aqueous slurry, i.e the microcapsule(s) is (are) dispersed in an aqueous phase.

[0027] By “amino-compound” it should be understood a compound having at least two reactive amine groups.

[0028] By “polyamide-based microcapsules”, “polyamide-based core-shell microcapsules” or “polyamide-based shell”, it means that the microcapsule's shell comprises a polyamide material. The wording “polyamide-based microcapsules” can also encompass a shell made of a composite comprising a polyamide material and another material, for example a protein as defined in the present invention.

“Polyamide-based microcapsules” and “polyamide microcapsules” are used indifferently in the present invention. “Polyamide-based shell” and “polyamide shell” are used indifferently in the present invention.

[0029] By “polyfunctional monomer”, it is meant a molecule that, as unit, reacts or binds chemically to form a polymer or a supramolecular polymer. The polyfunctional monomer of the invention has at least two functional groups that are capable to react with or bind to functional groups of another component and/or are capable to polymerize to form a polymeric shell.

[0030] It has been found that core-shell microcapsules, preferably polyamide-based microcapsules

with overall good performance in challenging bases could be obtained.

Core-Shell Microcapsule

[0031] A first object of the invention is a core-shell microcapsule comprising: [0032] a core comprising a hydrophobic material, preferably a perfume oil, and [0033] a polymeric shell comprising a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof.

[0034] According to an embodiment, the protein in the polymeric shell is cross-linked.

[0035] According to an embodiment, the protein in the polymeric shell is partially cross-linked.

[0036] According to an embodiment, the protein in the polymeric shell is not cross-linked.

[0037] According to an embodiment, the polymeric shell comprises a polymerized polyfunctional monomer.

Hydrophobic Material

[0038] According to an embodiment, the core is an oil-based core.

[0039] The hydrophobic material according to the invention can be “inert” material like solvents or active ingredients.

[0040] By “hydrophobic material”, it is meant any hydrophobic material which forms a two-phase dispersion when mixed with water. The hydrophobic material is typically liquid at about 20° C.

[0041] According to an embodiment, the hydrophobic material is a hydrophobic active ingredient.

[0042] When the hydrophobic materials is an active ingredient, it is preferably chosen from the group consisting of flavors, flavor ingredients, perfumes, perfume ingredients, nutraceuticals, cosmetics, pest control agents, biocide actives and mixtures thereof.

[0043] According to a particular embodiment, the hydrophobic material comprises a phase change material (PCM).

[0044] According to a particular embodiment, the hydrophobic material comprises a mixture of a perfume with another ingredient selected from the group consisting of nutraceuticals, cosmetics, pest control agents and biocide actives.

[0045] According to a particular embodiment, the hydrophobic material comprises a mixture of biocide actives with another ingredient selected from the group consisting of perfumes, nutraceuticals, cosmetics, pest control agents.

[0046] According to a particular embodiment, the hydrophobic material comprises a mixture of pest control agents with another ingredient selected from the group consisting of perfumes, nutraceuticals, cosmetics, biocide actives.

[0047] According to a particular embodiment, the hydrophobic material comprises a perfume.

[0048] According to a particular embodiment, the hydrophobic material consists of a perfume.

[0049] According to a particular embodiment, the hydrophobic material consists of biocide actives.

[0050] According to a particular embodiment, the hydrophobic material consists of pest control agents.

[0051] By “perfume” (or also “perfume oil”) what is meant here is an ingredient or a composition that is a liquid at about 20° C. According to any one of the above embodiments said perfume oil can be a perfuming ingredient alone or a mixture of ingredients in the form of a perfuming composition. As a “perfuming ingredient” it is meant here a compound, which is used for the primary purpose of conferring or modulating an odor. In other words such an ingredient, to be considered as being a perfuming one, must be recognized by a person skilled in the art as being able to at least impart or modify in a positive or pleasant way the odor of a composition, and not just as having an odor. For the purpose of the present invention, perfume oil also includes a combination of perfuming ingredients with substances which together improve, enhance or modify the delivery of the perfuming ingredients, such as perfume precursors, modulators, emulsions or dispersions, as well as combinations which impart an additional benefit beyond that of modifying or imparting an odor, such as long-lastingness, blooming, malodor counteraction, antimicrobial

effect, microbial stability, pest control.

[0052] The nature and type of the perfuming ingredients present in the oil phase do not warrant a more detailed description here, which in any case would not be exhaustive, the skilled person being able to select them on the basis of its general knowledge and according to intended use or application and the desired organoleptic effect. In general terms, these perfuming ingredients belong to chemical classes as varied as alcohols, aldehydes, ketones, esters, ethers, acetates, nitriles, terpenoids, nitrogenous or sulfurous heterocyclic compounds and essential oils (for example Thyme oil), and said perfuming co-ingredients can be of natural or synthetic origin. Many of these co-ingredients are in any case listed in reference texts such as the book by S. Arctander, *Perfume and Flavor Chemicals*, 1969, Montclair, New Jersey, USA, or its more recent versions, or in other works of a similar nature, as well as in the abundant patent literature in the field of perfumery.

[0053] In particular one may cite perfuming ingredients which are commonly used in perfume formulations, such as: [0054] Aldehydic ingredients: decanal, dodecanal, 2-methyl-undecanal, 10-undecenal, octanal, nonanal and/or nonenal; [0055] Aromatic-herbal ingredients: eucalyptus oil, camphor, eucalyptol, 5-methyltricyclo[6.2.1.0^{sup}.2,7]undecan-4-one, 1-methoxy-3-hexanethiol, 2-ethyl-4,4-dimethyl-1,3-oxathiane, 2,2,7/8,9/10-tetramethylspiro[5.5]undec-8-en-1-one, menthol and/or alpha-pinene; [0056] Balsamic ingredients: coumarin, ethylvanillin and/or vanillin; [0057] Citrus ingredients: dihydromyrcenol, citral, orange oil, linalyl acetate, citronellyl nitrile, orange terpenes, limonene, 1-p-menthen-8-yl acetate and/or 1,4 (8)-p-menthadiene; [0058] Floral ingredients: methyl dihydrojasmonate, linalool, citronellol, phenylethanol, 3-(4-tert-butylphenyl)-2-methylpropanal, hexylcinnamic aldehyde, benzyl acetate, benzyl salicylate, tetrahydro-2-isobutyl-4-methyl-4 (2H)-pyranol, beta ionone, methyl 2-(methylamino)benzoate, (E)-3-methyl-4-(2,6,6-trimethyl-2-cyclohexen-1-yl)-3-buten-2-one, (1E)-1-(2,6,6-trimethyl-2-cyclohexen-1-yl)-1-penten-3-one, 1-(2,6,6-trimethyl-1,3-cyclohexadien-1-yl)-2-buten-1-one, (2E)-1-(2,6,6-trimethyl-2-cyclohexen-1-yl)-2-buten-1-one, (2E)-1-[2,6,6-trimethyl-3-cyclohexen-1-yl]-2-buten-1-one, (2E)-1-(2,6,6-trimethyl-1-cyclohexen-1-yl)-2-buten-1-one, 3-(3,3/1,1-dimethyl-5-indanyl) propanal, 2,5-dimethyl-2-indanmethanol, 2,6,6-trimethyl-3-cyclohexene-1-carboxylate, 3-(4,4-dimethyl-1-cyclohexen-1-yl) propanal, hexyl salicylate, 3,7-dimethyl-1,6-nonadien-3-ol, 3-(4-isopropylphenyl)-2-methylpropanal, verdyl acetate, geraniol, p-menth-1-en-8-ol, 4-(1,1-dimethylethyl)-1-cyclohexyle acetate, 1,1-dimethyl-2-phenylethyl acetate, 4-cyclohexyl-2-methyl-2-butanol, amyl salicylate, high cis methyl dihydrojasmonate, 3-methyl-5-phenyl-1-pentanol, verdyl propionate, geranyl acetate, tetrahydro linalool, cis-7-p-menthanol, propyl(S)-2-(1,1-dimethylpropoxy) propanoate, 2-methoxynaphthalene, 2,2,2-trichloro-1-phenylethyl acetate, 4/3-(4-hydroxy-4-methylpentyl)-3-cyclohexene-1-carbaldehyde, amylcinnamic aldehyde, 8-decen-5-olide, 4-phenyl-2-butanone, isononyl acetate, 4-(1,1-dimethylethyl)-1-cyclohexyl acetate, verdyl isobutyrate and/or mixture of methylionones isomers; [0059] Fruity ingredients: gamma-undecalactone, 2,2,5-trimethyl-5-pentylcyclopentanone, 2-methyl-4-propyl-1,3-oxathiane, 4-decanolide, ethyl 2-methyl-pentanoate, hexyl acetate, ethyl 2-methylbutanoate, gamma-nonolactone, allyl heptanoate, 2-phenoxyethyl isobutyrate, ethyl 2-methyl-1,3-dioxolane-2-acetate, diethyl 1,4-cyclohexanedicarboxylate, 3-methyl-2-hexen-1-yl acetate, 1-[3,3-dimethylcyclohexyl]ethyl[3-ethyl-2-oxiranyl]acetate and/or diethyl 1,4-cyclohexane dicarboxylate; [0060] Green ingredients: 2-methyl-3-hexanone (E)-oxime, 2,4-dimethyl-3-cyclohexene-1-carbaldehyde, 2-tert-butyl-1-cyclohexyl acetate, styrallyl acetate, allyl (2-methylbutoxy)acetate, 4-methyl-3-decen-5-ol, diphenyl ether, (Z)-3-hexen-1-ol and/or 1-(5,5-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one; [0061] Musk ingredients: 1,4-dioxa-5,17-cycloheptadecanedione, (Z)-4-cyclopentadecen-1-one, 3-methylcyclopentadecanone, 1-oxa-12-cyclohexadecen-2-one, 1-oxa-13-cyclohexadecen-2-one, (9Z)-9-cycloheptadecen-1-one, 2-[(1S)-1-[(1R)-3,3-dimethylcyclohexyl]ethoxy]-2-oxoethyl propionate, 3-methyl-5-cyclopentadecen-1-ol, 4,6,6,7,8,8-hexamethyl-1,3,4,6,7,8-hexahydrocyclopenta[g]isochromene, one, (1S,1'R)-2-[1-(3',3'-dimethyl-1'-

cyclohexyl) ethoxy]-2-methylpropyl propanoate, oxacyclohexadecan-2-one and/or (1S,1'R)-[1-(3',3'-dimethyl-1'-cyclohexyl) ethoxycarbonyl]methyl propanoate; [0062] Woody ingredients: 1-[(1RS,6SR)-2,2,6-trimethylcyclohexyl]-3-hexanol, 3,3-dimethyl-5-[(1R)-2,2,3-trimethyl-3-cyclopenten-1-yl]-4-penten-2-ol, 3,4'-dimethylspiro[oxirane-2,9'-tricyclo[6.2.1.0.sup.2,7]undec[4]ene, (1-ethoxyethoxy)cyclododecane, 2,2,9,11-tetramethylspiro[5.5]undec-8-en-1-yl acetate, 1-(octahydro-2,3,8,8-tetramethyl-2-naphthalenyl)-1-ethanone, patchouli oil, terpenes fractions of patchouli oil, Clearwood®, (1'R,E)-2-ethyl-4-(2',2',3'-trimethyl-3'-cyclopenten-1'-yl)-2-buten-1-ol, 2-ethyl-4-(2,2,3-trimethyl-3-cyclopenten-1-yl)-2-buten-1-ol, methyl cedryl ketone, 5-(2,2,3-trimethyl-3-cyclopentenyl)-3-methylpentan-2-ol, 1-(2,3,8,8-tetramethyl-1,2,3,4,6,7,8,8a-octahydronaphthalen-2-yl) ethan-1-one and/or isobornyl acetate; [0063] Other ingredients (e.g. amber, powdery spicy or watery): dodecahydro-3a,6,6,9a-tetramethyl-naphtho[2,1-b]furan and any of its stereoisomers, heliotropin, anisic aldehyde, eugenol, cinnamic aldehyde, clove oil, 3-(1,3-benzodioxol-5-yl)-2-methylpropanal, 7-methyl-2H-1,5-benzodioxepin-3 (4H)-one, 2,5,5-trimethyl-1,2,3,4,4a,5,6,7-octahydro-2-naphthalenol, 1-phenylvinyl acetate, 6-methyl-7-oxa-1-thia-4-azaspiro[4.4]nonane and/or 3-(3-isopropyl-1-phenyl) butanal.

[0064] It is also understood that said ingredients may also be compounds known to release in a controlled manner various types of perfuming compounds also known as properfume or profragrance. Non-limiting examples of suitable properfumes may include 4-(dodecylthio)-4-(2,6,6-trimethyl-2-cyclohexen-1-yl)-2-butanone, 4-(dodecylthio)-4-(2,6,6-trimethyl-1-cyclohexen-1-yl)-2-butanone, 3-(dodecylthio)-1-(2,6,6-trimethyl-3-cyclohexen-1-yl)-1-butanone, 2-(dodecylthio) octan-4-one, 2-phenylethyl oxo (phenyl)acetate, 3,7-dimethylocta-2,6-dien-1-yl oxo (phenyl)acetate, (Z)-hex-3-en-1-yl oxo (phenyl)acetate, 3,7-dimethyl-2,6-octadien-1-yl hexadecanoate, bis(3,7-dimethylocta-2,6-dien-1-yl) succinate, (2-((2-methylundec-1-en-1-yl)oxy)ethyl)benzene, 1-methoxy-4-(3-methyl-4-phenethoxybut-3-en-1-yl)benzene, (3-methyl-4-phenethoxybut-3-en-1-yl)benzene, 1-(((Z)-hex-3-en-1-yl)oxy)-2-methylundec-1-ene, (2-((2-methylundec-1-en-1-yl)oxy)ethoxy)benzene, 2-methyl-1-(octan-3-yloxy) undec-1-ene, 1-methoxy-4-(1-phenethoxyprop-1-en-2-yl)benzene, 1-methyl-4-(1-phenethoxyprop-1-en-2-yl)benzene, 2-(1-phenethoxyprop-1-en-2-yl) naphthalene, (2-phenethoxyvinyl)benzene, 2-(1-((3,7-dimethyloct-6-en-1-yl)oxy) prop-1-en-2-yl) naphthalene, (2-((2-pentylcyclopentylidene) methoxy)ethyl)benzene, 4-allyl-2-methoxy-1-((2-methoxy-2-phenylvinyl)oxy)benzene, (2-((2-heptylcyclopentylidene) methoxy)ethyl)benzene, 1-isopropyl-4-methyl-2-((2-pentylcyclopentylidene) methoxy)benzene, 2-methoxy-1-((2-pentylcyclopentylidene) methoxy)-4-propylbenzene, 3-methoxy-4-((2-methoxy-2-phenylvinyl)oxy)benzaldehyde, 4-((2-(hexyloxy)-2-phenylvinyl)oxy)-3-methoxybenzaldehyde or a mixture thereof.

[0065] The perfuming ingredients may be dissolved in a solvent of current use in the perfume industry. The solvent is preferably not an alcohol. Examples of such solvents are diethyl phthalate, isopropyl myristate, Abalyn® (rosin resins, available from Eastman), benzyl benzoate, ethyl citrate, triethyl citrate, limonene or other terpenes, or isoparaffins. Preferably, the solvent is very hydrophobic and highly sterically hindered, like for example Abalyn® or benzyl benzoate. Preferably the perfume comprises less than 30% of solvent. More preferably the perfume comprises less than 20% and even more preferably less than 10% of solvent, all these percentages being defined by weight relative to the total weight of the perfume. Most preferably, the perfume is essentially free of solvent.

[0066] Preferred perfuming ingredients are those having a high steric hindrance and in particular those from one of the following groups: [0067] Group 1: perfuming ingredients comprising a cyclohexane, cyclohexene, cyclohexanone or cyclohexenone ring substituted with at least one linear or branched C.sub.1 to C.sub.4 alkyl or alkenyl substituent; [0068] Group 2: perfuming ingredients comprising a cyclopentane, cyclopentene, cyclopentanone or cyclopentenone ring substituted with at least one linear or branched C.sub.4 to C.sub.8 alkyl or alkenyl substituent;

[0069] Group 3: perfuming ingredients comprising a phenyl ring or perfuming ingredients comprising a cyclohexane, cyclohexene, cyclohexanone or cyclohexenone ring substituted with at least one linear or branched C.sub.5 to C.sub.8 alkyl or alkenyl substituent or with at least one phenyl substituent and optionally one or more linear or branched C.sub.1 to C.sub.3 alkyl or alkenyl substituents; [0070] Group 4: perfuming ingredients comprising at least two fused or linked C.sub.5 and/or C.sub.6 rings; [0071] Group 5: perfuming ingredients comprising a camphor-like ring structure; [0072] Group 6: perfuming ingredients comprising at least one C.sub.7 to C.sub.20 ring structure; [0073] Group 7: perfuming ingredients having a logP value above 3.5 and comprising at least one tert-butyl or at least one trichloromethyl substituent;

[0074] Examples of ingredients from each of these groups are: [0075] Group 1: 2,4-dimethyl-3-cyclohexene-1-carbaldehyde (origin: Firmenich SA, Geneva, Switzerland), isocyclocitral, menthone, isomenthone, methyl 2,2-dimethyl-6-methylene-1-cyclohexanecarboxylate (origin: Firmenich SA, Geneva, Switzerland), nerone, terpineol, dihydroterpineol, terpenyl acetate, dihydroterpenyl acetate, dipentene, eucalyptol, hexylate, rose oxide, (S)-1,8-p-menthadiene-7-ol (origin: Firmenich SA, Geneva, Switzerland), 1-p-menthene-4-ol, (1RS,3RS,4SR)-3-p-mentanyl acetate, (1R,2S,4R)-4,6,6-trimethyl-bicyclo[3,1,1]heptan-2-ol, tetrahydro-4-methyl-2-phenyl-2H-pyran (origin: Firmenich SA, Geneva, Switzerland), cyclohexyl acetate, cyclanol acetate, 1,4-cyclohexane diethyldicarboxylate (origin: Firmenich SA, Geneva, Switzerland), (3RS,3aRS,6SR,7ASR)-perhydro-3,6-dimethyl-benzo[B]furan-2-one (origin: Firmenich SA, Geneva, Switzerland), ((6R)-perhydro-3,6-dimethyl-benzo[B]furan-2-one (origin: Firmenich SA, Geneva, Switzerland), 2,4,6-trimethyl-4-phenyl-1,3-dioxane, 2,4,6-trimethyl-3-cyclohexene-1-carbaldehyde; [0076] Group 2: (E)-3-methyl-5-(2,2,3-trimethyl-3-cyclopenten-1-yl)-4-penten-2-ol (origin: Givaudan SA, Vernier, Switzerland), (1'R,E)-2-ethyl-4-(2',2',3'-trimethyl-3'-cyclopenten-1'-yl)-2-buten-1-ol (origin: Firmenich SA, Geneva, Switzerland), (1'R,E)-3,3-dimethyl-5-(2',2',3'-trimethyl-3'-cyclopenten-1'-yl)-4-penten-2-ol (origin: Firmenich SA, Geneva, Switzerland), 2-heptylcyclopentanone, methyl-cis-3-oxo-2-pentyl-1-cyclopentane acetate (origin: Firmenich SA, Geneva, Switzerland), 2,2,5-trimethyl-5-pentyl-1-cyclopentanone (origin: Firmenich SA, Geneva, Switzerland), 3,3-dimethyl-5-(2,2,3-trimethyl-3-cyclopenten-1-yl)-4-penten-2-ol (origin: Firmenich SA, Geneva, Switzerland), 3-methyl-5-(2,2,3-trimethyl-3-cyclopenten-1-yl)-2-pentanol (origin: Givaudan SA, Vernier, Switzerland); [0077] Group 3: damascones, 1-(5,5-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one (origin: Firmenich SA, Geneva, Switzerland), (1'R)-2-[2-(4'-methyl-3'-cyclohexen-1'-yl) propyl]cyclopentanone, alpha-ionone, beta-ionone, damascenone, mixture of 1-(5,5-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one and 1-(3,3-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one (origin: Firmenich SA, Geneva, Switzerland), 1-(2,6,6-trimethyl-1-cyclohexen-1-yl)-2-buten-1-one (origin: Firmenich SA, Geneva, Switzerland), (1S,1'R)-[1-(3',3'-Dimethyl-1'-cyclohexyl) ethoxycarbonyl]methyl propanoate (origin: Firmenich SA, Geneva, Switzerland), 2-tert-butyl-1-cyclohexyl acetate (origin: International Flavors and Fragrances, USA), 1-(2,2,3,6-tetramethyl-cyclohexyl)-3-hexanol (origin: Firmenich SA, Geneva, Switzerland), trans-1-(2,2,6-trimethyl-1-cyclohexyl)-3-hexanol (origin: Firmenich SA, Geneva, Switzerland), (E)-3-methyl-4-(2,6,6-trimethyl-2-cyclohexen-1-yl)-3-buten-2-one, terpenyl isobutyrate, 4-(1,1-dimethylethyl)-1-cyclohexyl acetate (origin: Firmenich SA, Geneva, Switzerland), 8-methoxy-1-p-menthene, (1S,1'R)-2-[1-(3',3'-dimethyl-1'-cyclohexyl) ethoxy]-2-methylpropyl propanoate (origin: Firmenich SA, Geneva, Switzerland), para tert-butylcyclohexanone, menthenethiol, 1-methyl-4-(4-methyl-3-pentenyl)-3-cyclohexene-1-carbaldehyde, allyl cyclohexylpropionate, cyclohexyl salicylate, 2-methoxy-4-methylphenyl methyl carbonate, ethyl 2-methoxy-4-methylphenyl carbonate, 4-ethyl-2-methoxyphenyl methyl carbonate; [0078] Group 4: Methyl cedryl ketone (origin: International Flavors and Fragrances, USA), a mixture of (1RS,2SR,6RS,7RS,8SR)-tricyclo[5.2.1.0.sup.2,6]dec-3-en-8-yl 2-methylpropanoate and (1RS,2SR,6RS,7RS,8SR)-tricyclo[5.2.1.0.sup.2,6]dec-4-en-8-yl 2-methylpropanoate, vetyverol, vetyverone, 1-(octahydro-2,3,8,8-tetramethyl-2-naphtalenyl)-1-ethanone (origin: International Flavors and Fragrances, USA), (5RS,9RS,10SR)-2,6,9,10-

tetramethyl-1-oxaspiro[4.5]deca-3,6-diene and the (5RS,9SR,10RS) isomer, 6-ethyl-2,10,10-trimethyl-1-oxaspiro[4.5]deca-3,6-diene, 1,2,3,5,6,7-hexahydro-1,1,2,3,3-pentamethyl-4-indenone (origin: International Flavors and Fragrances, USA), a mixture of 3-(3,3-dimethyl-5-indanyl) propanal and 3-(1,1-dimethyl-5-indanyl) propanal (origin: Firmenich SA, Geneva, Switzerland), 3',4-dimethyl-tricyclo[6.2.1.0 (2,7)]undec-4-ene-9-spiro-2'-oxirane (origin: Firmenich SA, Geneva, Switzerland), 9/10-ethyldiene-3-oxatricyclo[6.2.1.0 (2,7)]undecane, (perhydro-5,5,8A-trimethyl-2-naphthalenyl acetate (origin: Firmenich SA, Geneva, Switzerland), octalynol, (dodecahydro-3a,6,6,9a-tetramethyl-naphtho[2,1-b]furan, origin: Firmenich SA, Geneva, Switzerland), tricyclo[5.2.1.0 (2,6)]dec-3-en-8-yl acetate and tricyclo[5.2.1.0 (2,6)]dec-4-en-8-yl acetate as well as tricyclo[5.2.1.0 (2,6)]dec-3-en-8-yl propanoate and tricyclo[5.2.1.0 (2,6)]dec-4-en-8-yl propanoate, (+)-(1S,2S,3S)-2,6,6-trimethyl-bicyclo[3.1.1]heptane-3-spiro-2'-cyclohexen-4'-one; [0079] Group 5: camphor, borneol, isobornyl acetate, 8-isopropyl-6-methyl-bicyclo[2.2.2]oct-5-ene-2-carbaldehyde, pinene, camphene, 8-methoxycedrane, (8-methoxy-2,6,6,8-tetramethyl-tricyclo[5.3.1.0 (1,5)]undecane (origin: Firmenich SA, Geneva, Switzerland), cedrene, cedrenol, cedrol, mixture of 9-ethylidene-3-oxatricyclo[6.2.1.0 (2,7)]undecan-4-one and 10-ethylidene-3-oxatricyclo[6.2.1.0.sup.2,7]undecan-4-one (origin: Firmenich SA, Geneva, Switzerland), 3-methoxy-7,7-dimethyl-10-methylene-bicyclo[4.3.1]decane (origin: Firmenich SA, Geneva, Switzerland); [0080] Group 6: (trimethyl-13-oxabicyclo-[10.1.0]-trideca-4,8-diene (origin: Firmenich SA, Geneva, Switzerland), 9-hexadecen-16-olide (origin: Firmenich SA, Geneva, Switzerland), pentadecenolide (origin: Firmenich SA, Geneva, Switzerland), 3-methyl-(4/5)-cyclopentadecenone, (origin: Firmenich SA, Geneva, Switzerland), 3-methylcyclopentadecanone (origin: Firmenich SA, Geneva, Switzerland), pentadecanolide (origin: Firmenich SA, Geneva, Switzerland), cyclopentadecanone (origin: Firmenich SA, Geneva, Switzerland), 1-ethoxyethoxy)cyclododecane (origin: Firmenich SA, Geneva, Switzerland), 1,4-dioxacycloheptadecane-5,17-dione, 4,8-cyclododecadien-1-one; [0081] Group 7: (+-)-2-methyl-3-[4-(2-methyl-2-propanyl)phenyl]propanal (origin: Givaudan SA, Vernier, Switzerland), 2,2,2-trichloro-1-phenylethyl acetate.

[0082] Preferably, the perfume comprises at least 30%, preferably at least 50%, more preferably at least 60% of ingredients selected from Groups 1 to 7, as defined above. More preferably said perfume comprises at least 30%, preferably at least 50% of ingredients from Groups 3 to 7, as defined above. Most preferably said perfume comprises at least 30%, preferably at least 50% of ingredients from Groups 3, 4, 6 or 7, as defined above.

[0083] According to another preferred embodiment, the perfume comprises at least 30%, preferably at least 50%, more preferably at least 60% of ingredients having a logP above 3, preferably above 3.5 and even more preferably above 3.75.

[0084] According to a particular embodiment, the perfume used in the invention contains less than 10% of its own weight of primary alcohols, less than 15% of its own weight of secondary alcohols and less than 20% of its own weight of tertiary alcohols. Advantageously, the perfume used in the invention does not contain any primary alcohols and contains less than 15% of secondary and tertiary alcohols.

[0085] According to an embodiment, the oil phase (or the oil-based core) comprises: [0086] 25-100 wt % of a perfume oil comprising at least 15 wt % of high impact perfume raw materials having a $\text{Log } T \leq 4$, and [0087] 0-75 wt % of a density balancing material having a density greater than 1.07 g/cm³. "High impact perfume raw materials" should be understood as perfume raw materials having a $\text{Log } T \leq 4$. The odor threshold concentration of a chemical compound is determined in part by its shape, polarity, partial charges and molecular mass. For convenience, the odor threshold concentration is presented as the common logarithm of the threshold concentration, i.e., $\text{Log}[\text{Threshold}]$ ("LogT").

[0088] A "density balancing material" should be understood as a material having a density greater than 1.07 g/cm³ and having preferably low or no odor.

[0089] The odor threshold concentration of a perfuming compound is determined by using a gas chromatograph ("GC"). Specifically, the gas chromatograph is calibrated to determine the exact volume of the perfume oil ingredient injected by the syringe, the precise split ratio, and the hydrocarbon response using a hydrocarbon standard of known concentration and chain-length distribution. The air flow rate is accurately measured and, assuming the duration of a human inhalation to last 12 seconds, the sampled volume is calculated. Since the precise concentration at the detector at any point in time is known, the mass per volume inhaled is known and hence the concentration of the perfuming compound. To determine the threshold concentration, solutions are delivered to the sniff port at the back-calculated concentration. A panelist sniffs the GC effluent and identifies the retention time when odor is noticed. The average across all panelists determines the odor threshold concentration of the perfuming compound. The determination of odor threshold is described in more detail in C. Vuilleumier et al., *Multidimensional Visualization of Physical and Perceptual Data Leading to a Creative Approach in Fragrance Development*, Perfume & Flavorist, Vol. 33, September, 2008, pages 54-61.

[0090] The nature of high impact perfume raw materials having a Log T < 4 and density balancing material having a density greater than 1.07 g/cm³ are described in WO2018115250, the content of which are included by reference.

[0091] According to an embodiment, the high impact perfume raw materials having a Log T < -4 are selected from the group consisting of (+-)-1-methoxy-3-hexanethiol, 4-(4-hydroxy-1-phenyl)-2-butanone, 2-methoxy-4-(1-propenyl)-1-phenyl acetate, pyrazobutyle, 3-propylphenol, 1-(3-methyl-1-benzofuran-2-yl) ethanone, 2-(3-phenylpropyl)pyridine, 1-(3,3/5,5-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one, 1-(5,5-dimethyl-1-cyclohexen-1-yl)-4-penten-1-one, a mixture comprising (3RS,3aRS,6SR,7ASR)-perhydro-3,6-dimethyl-benzo[b]furan-2-one and (3SR,3aRS,6SR,7ASR)-perhydro-3,6-dimethyl-benzo[b]furan-2-one, (+-)-1-(5-ethyl-5-methyl-1-cyclohexen-1-yl)-4-penten-1-one, (1'S,3'R)-1-methyl-2-[(1',2',2'-trimethylbicyclo[3.1.0]hex-3'-yl)methyl]cyclopropyl}methanol, (+-)-3-mercaptohexyl acetate, (2E)-1-(2,6,6-trimethyl-1,3-cyclohexadien-1-yl)-2-buten-1-one, H-methyl-2h-1,5-benzodioxepin-3 (4H)-one, (2E,6Z)-2,6-nonadien-1-ol, (4Z)-4-dodecenal, (+-)-4-hydroxy-2,5-dimethyl-3 (2H)-furanone, methyl 2,4-dihydroxy-3,6-dimethylbenzoate, 3-methylindole, (+-)-perhydro-4alpha,8abeta-dimethyl-4a-naphthalenol, patchoulol, 2-methoxy-4-(1-propenyl) phenol, mixture comprising (+-)-5,6-dihydro-4-methyl-2-phenyl-2H-pyran and tetrahydro-4-methylene-2-phenyl-2H-pyran, mixture comprising 4-methylene-2-phenyltetrahydro-2H-pyran and (+-)-4-methyl-2-phenyl-3,6-dihydro-2H-pyran, 4-hydroxy-3-methoxybenzaldehyde, nonylenic aldehyde, 2-methoxy-4-propylphenol, 3-methyl-5-phenyl-2-pentenitrile, 1-(spiro[4.5]dec-6/7-en-7-yl)-4-penten-1-one (, 2-methoxynaphthalene, (-)-(3aR,5AS,9AS,9BR)-3a,6,6,9a-tetramethyldodecahydronaphtho[2,1-b]furan, 5-nonanolide, (3aR,5AS,9AS,9BR)-3a,6,6,9a-tetramethyldodecahydronaphtho[2,1-b]furan, 7-isopropyl-2H,4H-1,5-benzodioxepin-3-one, coumarin, 4-methylphenyl isobutyrate, (2E)-1-(2,6,6-trimethyl-1,3-cyclohexadien-1-yl)-2-buten-1-one, beta,2,2,3-tetramethyl-delta-methylene-3-cyclopentene-1-butanol, delta damascone ((2E)-1-[(1RS,2SR)-2,6,6-trimethyl-3-cyclohexen-1-yl]-2-buten-1-one), (+-)-3,6-dihydro-4,6-dimethyl-2-phenyl-2h-pyran, anisaldehyde, paracresol, 3-ethoxy-4-hydroxybenzaldehyde, methyl 2-aminobenzoate, ethyl methylphenylglycidate, octalactone gamma, ethyl 3-phenyl-2-propenoate, (-)-(2E)-2-ethyl-4-[(1R)-2,2,3-trimethyl-3-cyclopenten-1-yl]-2-buten-1-ol, paracresyl acetate, dodecalactone, tricyclone, (+)-(3R,5Z)-3-methyl-5-cyclopentadecen-1-one, undecalactone, (1R,4R)-8-mercapto-3-p-menthanone, (3S,3AS,6R,7AR)-3,6-dimethylhexahydro-1-benzofuran-2 (3H)-one, beta ionone, (+-)-6-pentyltetrahydro-2H-pyran-2-one, (3E,5Z)-1,3,5-undecatriene, 10-undecenal, (9E)-9-undecenal (9Z)-9-undecenal, (Z)-4-decenal, (+-)-ethyl 2-methylpentanoate, 1,2-diallyldisulfane, 2-tridecenitrile, 3-tridecenitrile, (+-)-2-ethyl-4,4-dimethyl-1,3-oxathiane, (+)-(3R,5Z)-3-methyl-5-cyclopentadecen-1-one, 3-(4-tert-butylphenyl) propanal, allyl (cyclohexyloxy)acetate, methyl naphthylketone, (+-)-(4E)-3-methyl-4-cyclopentadecen-1-one, (+-)-5E3-methyl-5-cyclopentadecen-1-one, cyclopropylmethyl 3-

hexenoate, (4E)-4-methyl-5-(4-methylphenyl)-4-pentenal, (+-)-1-(5-propyl-1,3-benzodioxol-2-yl) ethanone, 4-methyl-2-pentylpyridine, (+-)-(E)-3-methyl-4-(2,6,6-trimethyl-2-cyclohexen-1-yl)-3-buten-2-one, (3aRS,5aSR,9aSR,9bRS)-3a,6,6,9a-tetramethyldodecahydronaphtho[2,1-b]furan, (2S,5R)-5-methyl-2-(2-propanyl)cyclohexanone oxime, 6-hexyltetrahydro-2H-pyran-2-one, (+-)-3-(3-isopropyl-1-phenyl) butanal, methyl 2-(3-oxo-2-pentylcyclopentyl)acetate, 1-(2,6,6-trimethyl-1-cyclohex-2-enyl) pent-1-en-3-one, indol, 7-propyl-2H,4H-1,5-benzodioxepin-3-one, ethyl praline, (4-methylphenoxy) acetaldehyde, ethyl tricyclo[5.2.1.0.2,6]decane-2-carboxylate, (+)-(1'S,2S,E)-3,3-dimethyl-5-(2',2',3'-trimethyl-3'-cyclopenten-1'-yl)-4-penten-2-ol, (4E)-3,3-dimethyl-5-[(1R)-2,2,3-trimethyl-3-cyclopenten-1-yl]-4-penten-2-ol, 8-isopropyl-6-methyl-bicyclo[2.2.2]oct-5-ene-2-carbaldehyde, methylnonylacetaldehyde, 4-formyl-2-methoxyphenyl 2-methylpropanoate, (E)-4-decenal, (+-)-2-ethyl-4-(2,2,3-trimethyl-3-cyclopenten-1-yl)-2-buten-1-ol, (1R,5R)-4,7,7-trimethyl-6-thiabicyclo[3.2.1]oct-3-ene, (1R,4R,5R)-4,7,7-trimethyl-6-thiabicyclo[3.2.1]octane, (-)-(3R)-3,7-dimethyl-1,6-octadien-3-ol, (E)-3-phenyl-2-propenenitrile, 4-methoxybenzyl acetate, (E)-3-methyl-5-(2,2,3-trimethyl-3-cyclopenten-1-yl)-4-penten-2-ol, allyl (2/3-methylbutoxy)acetate, (+-)-(2E)-1-(2,6,6-trimethyl-2-cyclohexen-1-yl)-2-buten-1-one, (1E)-1-(2,6,6-trimethyl-1-cyclohexen-1-yl)-1-penten-3-one, and mixtures thereof.

[0092] According to an embodiment, perfume raw materials having a Log T $\leq$ 4 are chosen in the group consisting of aldehydes, ketones, alcohols, phenols, esters lactones, ethers, epoxydes, nitriles and mixtures thereof.

[0093] According to an embodiment, perfume raw materials having a Log T $\leq$ 4 comprise at least one compound chosen in the group consisting of alcohols, phenols, esters lactones, ethers, epoxydes, nitriles and mixtures thereof, preferably in amount comprised between 20 and 70% by weight based on the total weight of the perfume raw materials having a Log T $\leq$ 4.

[0094] According to an embodiment, perfume raw materials having a Log T $\leq$ 4 comprise between 20 and 70% by weight of aldehydes, ketones, and mixtures thereof based on the total weight of the perfume raw materials having a Log T $\leq$ 4.

[0095] The remaining perfume raw materials contained in the oil-based core may have therefore a Log T $\leq$ 4.

[0096] According to an embodiment, the perfume raw materials having a Log T $\leq$ 4 are chosen in the group consisting of ethyl 2-methylbutyrate, (E)-3-phenyl-2-propenyl acetate, (+-)-6/8-sec-butylquinoline, (+-)-3-(1,3-benzodioxol-5-yl)-2-methylpropanal, verdyl propionate, 1-(octahydro-2,3,8,8-tetramethyl-2-naphtalenyl)-1-ethanone, methyl 2-((1RS,2RS)-3-oxo-2-pentylcyclopentyl)acetate, (+-)-(E)-4-methyl-3-decen-5-ol, 2,4-dimethyl-3-cyclohexene-1-carbaldehyde, 1,3,3-trimethyl-2-oxabicyclo[2.2.2]octane, tetrahydro-4-methyl-2-(2-methyl-1-propenyl)-2H-pyran, dodecanal, 1-oxa-12/13-cyclohexadecen-2-one, (+-)-3-(4-isopropylphenyl)-2-methylpropanal, aldehyde C.sub.11, (+-)-2,6-dimethyl-7-octen-2-ol, allyl 3-cyclohexylpropanoate, (Z)-3-hexenyl acetate, 5-methyl-2-(2-propanyl)cyclohexanone, allyl heptanoate, 2-(2-methyl-2-propanyl)cyclohexyl acetate, 1,1-dimethyl-2-phenylethyl butyrate, geranyl acetate, neryl acetate, (+-)-1-phenylethyl acetate, 1,1-dimethyl-2-phenylethyl acetate, 3-methyl-2-butenyl acetate, ethyl 3-oxobutanoate, (2Z)-ethyl 3-hydroxy-2-butenate, 8-p-menthanol, 8-p-menthanyl acetate, 1-p-menthanyl acetate, (+-)-2-(4-methyl-3-cyclohexen-1-yl)-2-propanyl acetate, (+-)-2-methylbutyl butanoate, 2-{(1S)-1-[(1R)-3,3-dimethylcyclohexyl]ethoxy}-2-oxoethyl propionate, 3,5,6-trimethyl-3-cyclohexene-1-carbaldehyde, 2,4,6-trimethyl-3-cyclohexene-1-carbaldehyde, 2-cyclohexylethyl acetate, octanal, ethyl butanoate, (+-)-(3E)-4-(2,6,6-trimethyl-1/2-cyclohexen-1-yl)-3-buten-2-one, 1-[(1RS,6SR)-2,2,6-trimethylcyclohexyl]-3-hexanol, 1,3,3-trimethyl-2-oxabicyclo[2.2.2]octane, 1,3,3-trimethyl-2-oxabicyclo[2.2.2]octane, ethyl hexanoate, undecanal, decanal, 2-phenylethyl acetate, (1S,2S,4S)-1,7,7-trimethylbicyclo[2.2.1]heptan-2-ol, (1S,2R,4S)-1,7,7-trimethylbicyclo[2.2.1]heptan-2-ol, (+-)-3,7-dimethyl-3-octanol, 1-methyl-4-(2-propanylidene)cyclohexene, (+)-(R)-4-(2-methoxypropan-2-yl)-1-methylcyclohex-1-ene, verdyl acetate, (3R)-1-[(1R,6S)-2,2,6-trimethylcyclohexyl]-3-hexanol,

(3S)-1-[(1R,6S)-2,2,6-trimethylcyclohexyl]-3-hexanol, (+)-(1S,1'R)-2-[1-(3',3'-dimethyl-1'-cyclohexyl) ethoxy]-2-methylpropyl propanoate, and mixtures thereof.

[0097] According to an embodiment, the core comprises a perfume formulation comprising: [0098] 0 to 60 wt. % of a hydrophobic solvent (based on the total weight of the perfume formulation), [0099] 40 to 100 wt. % of a perfume oil (based on the total weight of the perfume formulation), wherein the perfume oil has at least two, preferably all of the following characteristics: [0100] at least 35%, preferably at least 40%, preferably at least 50%, more preferably at least 60% of perfuming ingredients having a log P above 3, preferably above 3.5, [0101] at least 20%, preferably at least 25%, preferably at least 30%, more preferably at least 40% of Bulky materials of groups 1 to 6, preferably 3 to 6 as herein defined and [0102] at least 15%, preferably at least 20%, more preferably at least 25%, even more preferably at least 30% of high impact perfume materials having a Log T $\leq$ 4, optionally, further hydrophobic active ingredients.

[0103] According to a particular embodiment, the perfume comprises 0 to 60 wt. % of a hydrophobic solvent.

[0104] According to a particular embodiment, the hydrophobic solvent is a density balancing material preferably chosen in the group consisting of benzyl salicylate, benzyl benzoate, cyclohexyl salicylate, benzyl phenylacetate, phenylethyl phenylacetate, triacetin, ethyl citrate, methyl and ethyl salicylate, benzyl cinnamate, and mixtures thereof.

[0105] In a particular embodiment, the hydrophobic solvent has Hansen Solubility Parameters compatible with entrapped perfume oil.

[0106] The term "Hansen solubility parameter" is understood refers to a solubility parameter approach proposed by Charles Hansen used to predict polymer solubility and was developed around the basis that the total energy of vaporization of a liquid consists of several individual parts. To calculate the "weighted Hansen solubility parameter" one must combine the effects of (atomic) dispersion forces, (molecular) permanent dipole-permanent dipole forces, and (molecular) hydrogen bonding (electron exchange). The weighted Hansen solubility parameter" is calculated as $(\delta D_{\text{sup}}^2 + \delta P_{\text{sup}}^2 + \delta H_{\text{sup}}^2)^{0.5}$, wherein δD is the Hansen dispersion value (also referred to in the following as the atomic dispersion fore), δP is the Hansen polarizability value (also referred to in the following as the dipole moment), and δH is the Hansen Hydrogen-bonding ("h-bonding") value (also referred to in the following as hydrogen bonding). For a more detailed description of the parameters and values, see Charles Hansen, The Three Dimensional Solubility Parameter and Solvent Diffusion Coefficient, Danish Technical Press (Copenhagen, 1967).

[0107] Euclidean difference in solubility parameter between a fragrance and a solvent is calculated as $(4 * (\delta D_{\text{sub}}^{\text{solvent}} - \delta D_{\text{sub}}^{\text{fragrance}})^2 + (\delta P_{\text{sub}}^{\text{solvent}} - \delta P_{\text{sub}}^{\text{fragrance}})^2 + (\delta H_{\text{sub}}^{\text{solvent}} - \delta H_{\text{sub}}^{\text{fragrance}})^2)^{0.5}$, in which $\delta D_{\text{sub}}^{\text{solvent}}$, $\delta P_{\text{sub}}^{\text{solvent}}$, and $\delta H_{\text{sub}}^{\text{solvent}}$, are the Hansen dispersion value, Hansen polarizability value, and Hansen h-bonding values of the solvent, respectively; and $\delta D_{\text{sub}}^{\text{fragrance}}$, $\delta P_{\text{sub}}^{\text{fragrance}}$, and $\delta H_{\text{sub}}^{\text{fragrance}}$ are the Hansen dispersion value, Hansen polarizability value, and Hansen h-bonding values of the fragrance, respectively.

[0108] In a particular embodiment, the perfume oil and the hydrophobic solvent have at least two Hansen solubility parameters selected from a first group consisting of: an atomic dispersion force (δD) from 12 to 20, a dipole moment (δP) from 1 to 8, and a hydrogen bonding (δH) from 2.5 to 11.

[0109] In a particular embodiment, the perfume oil and the hydrophobic solvent have at least two Hansen solubility parameters selected from a second group consisting of: an atomic dispersion force (δD) from 12 to 20, preferably from 14 to 20, a dipole moment (δP) from 1 to 8, preferably from 1 to 7, and a hydrogen bonding (δH) from 2.5 to 11, preferably from 4 to 11.

[0110] In a particular embodiment, at least 90% of the perfume oil, preferably at least 95% of the

perfume oil, most preferably at least of 98% of the perfume oil has at least two Hansen solubility parameters selected from a first group consisting of: an atomic dispersion force (δD) from 12 to 20, a dipole moment (δP) from 1 to 8, and a hydrogen bonding (δH) from 2.5 to 11.

[0111] In a particular embodiment, the perfume oil and the hydrophobic solvent have at least two Hansen solubility parameters selected from a second group consisting of: an atomic dispersion force (δD) from 12 to 20, preferably from 14 to 20, a dipole moment (δP) from 1 to 8, preferably from 1 to 7, and a hydrogen bonding (δH) from 2.5 to 11, preferably from 4 to 11.

[0112] According to an embodiment, the perfuming formulation comprises a fragrance modulator (that can be used in addition to the hydrophobic solvent when present or as substitution of the hydrophobic solvent when there is no hydrophobic solvent).

[0113] Preferably, the fragrance modulator is defined as a fragrance material with [0114] i. a vapor pressure of less than 0.0008 Torr at 22° C.; [0115] ii. a clogP of 3.5 and higher, preferable 4.0 and higher and more preferable 4.5 [0116] iii. at least two Hansen solubility parameters selected from a first group consisting of: an atomic dispersion force from 12 to 20, a dipole moment from 1 to 7, and a hydrogen bonding from 2.5 to 11, [0117] iv. at least two Hansen solubility parameters selected from a second group consisting of: an atomic dispersion force from 14 to 20, a dipole moment from 1 to 8, and a hydrogen bonding from 4 to 11, when in solution with a compound having a vapor pressure range of 0.0008 to 0.08 Torr at 22° C.

[0118] Preferably, as examples the following ingredients can be listed as modulators but the list is not limited to the following materials: alcohol C12, oxacyclohexadec-12/13-en-2-one, 3-[(2',2',3'-trimethyl-3'-cyclopenten-1'-yl) methoxy]-2-butanol, cyclohexadecanone, (Z)-4-cyclopentadecen-1-one, cyclopentadecanone, (8Z)-oxacycloheptadec-8-en-2-one, 2-[5-(tetrahydro-5-methyl-5-vinyl-2-furyl)-tetrahydro-5-methyl-2-furyl]-2-propanol, muguet aldehyde, 1,5,8-trimethyl-13-oxabicyclo[10.1.0]trideca-4,8-diene, (+-)-4,6,6,7,8,8-hexamethyl-1,3,4,6,7,8-hexahydrocyclopenta[g]isochromene, (+)-(1S,2S,3S,5R)-2,6,6-trimethylspiro[bicyclo[3.1.1]heptane-3,l'-cyclohexane]-2'-en-4'-one, oxacyclohexadecan-2-one, 2-{(1S)-1-[(1R)-3,3-dimethylcyclohexyl]ethoxy}-2-oxoethyl propionate, (+)-(4R,4aS,6R)-4,4a-dimethyl-6-(1-propen-2-yl)-4,4a,5,6,7,8-hexahydro-2 (3H)-naphthalenone, amylcinnamic aldehyde, hexylcinnamic aldehyde, hexyl salicylate, (1E)-1-(2,6,6-trimethyl-1-cyclohexen-1-yl)-1,6-heptadien-3-one, (9Z)-9-cycloheptadecen-1-one.

[0119] According to a particular embodiment, the hydrophobic material is free of any active ingredient (such as perfume). According to this particular embodiment, it comprises, preferably consists of hydrophobic solvents, preferably chosen in the group consisting of isopropyl myristate, tryglycerides (e.g. Neobee® MCT oil, vegetable oils), D-limonene, silicone oil, mineral oil, and mixtures thereof with optionally hydrophilic solvents preferably chosen in the group consisting of 1,4-butanediol, benzyl alcohol, triethyl citrate, triacetin, benzyl acetate, ethyl acetate, propylene glycol (1,2-propanediol), 1,3-propanediol, dipropylene glycol, glycerol, glycol ethers and mixtures thereof.

[0120] The term “biocide” refers to a chemical substance capable of killing living organisms (e.g. microorganisms) or reducing or preventing their growth and/or accumulation. Biocides are commonly used in medicine, agriculture, forestry, and in industry where they prevent the fouling of, for example, water, agricultural products including seed, and oil pipelines. A biocide can be a pesticide, including a fungicide, herbicide, insecticide, algicide, molluscicide, miticide and rodenticide; and/or an antimicrobial such as a germicide, antibiotic, antibacterial, antiviral, antifungal, antiprotozoal and/or antiparasite.

[0121] As used herein, a “pest control agent” indicates a substance that serves to repel or attract pests, to decrease, inhibit or promote their growth, development or their activity. Pests refer to any living organism, whether animal, plant or fungus, which is invasive or troublesome to plants or animals, pests include insects notably arthropods, mites, spiders, fungi, weeds, bacteria and other microorganisms.

[0122] By “flavor oil”, it is meant here a flavoring ingredient or a mixture of flavoring ingredients, solvents or adjuvants of current use for the preparation of a flavoring formulation, i.e. a particular mixture of ingredients which is intended to be added to an edible composition or chewable product to impart, improve or modify its organoleptic properties, in particular its flavor and/or taste. Flavoring ingredients are well known to a person skilled in the art and their nature does not warrant a detailed description here, which in any case would not be exhaustive, the skilled flavorist being able to select them on the basis of his general knowledge and according to the intended use or application and the organoleptic effect it is desired to achieve. Many of these flavoring ingredients are listed in reference texts such as in the book by S. Arctander, *Perfume and Flavor Chemicals*, 1969, Montclair, N.J., USA, or its more recent versions, or in other works of similar nature such as *Fenaroli's Handbook of Flavor Ingredients*, 1975, CRC Press or *Synthetic Food Adjuncts*, 1947, by M. B. Jacobs, van Nostrand Co., Inc. Solvents and adjuvants of current use for the preparation of a flavoring formulation are also well known in the art.

[0123] In a particular embodiment, the flavor is a mint flavor. In a more particular embodiment, the mint is selected from the group consisting of peppermint and spearmint.

[0124] In a further embodiment, the flavor is a cooling agent or mixtures thereof.

[0125] In another embodiment, the flavor is a menthol flavor.

[0126] Flavors that are derived from or based on fruits where citric acid is the predominant, naturally-occurring acid include but are not limited to, for example, citrus fruits (e.g. lemon, lime), limonene, strawberry, orange, and pineapple. In one embodiment, the flavors food is lemon, lime or orange juice extracted directly from the fruit. Further embodiments of the flavor comprise the juice or liquid extracted from oranges, lemons, grapefruits, key limes, citrons, clementines, mandarins, tangerines, and any other citrus fruit, or variation or hybrid thereof. In a particular embodiment, the flavor comprises a liquid extracted or distilled from oranges, lemons, grapefruits, key limes, citrons, clementines, mandarins, tangerines, any other citrus fruit or variation or hybrid thereof, pomegranates, kiwifruits, watermelons, apples, bananas, blueberries, melons, ginger, bell peppers, cucumbers, passion fruits, mangos, pears, tomatoes, and strawberries.

[0127] In a particular embodiment, the flavor comprises a composition that comprises limonene, in a particular embodiment, the composition is a citrus that further comprises limonene.

[0128] In another particular embodiment, the flavor comprises a flavor selected from the group comprising strawberry, orange, lime, tropical, berry mix, and pineapple.

[0129] The phrase flavor includes not only flavors that impart or modify the smell of foods but include taste imparting or modifying ingredients. The latter do not necessarily have a taste or smell themselves but are capable of modifying the taste that other ingredients provides, for instance, salt enhancing ingredients, sweetness enhancing ingredients, umami enhancing ingredients, bitterness blocking ingredients and so on.

[0130] In a further embodiment, suitable sweetening components may be included in the particles described herein. In a particular embodiment, a sweetening component is selected from the group consisting of sugar (e.g., but not limited to sucrose), a *stevia* component (such as but not limited to stevioside or rebaudioside A), sodium cyclamate, aspartame, sucralose, sodium saccharine, and Acesulfam K or mixtures thereof.

Polymeric Shell

[0131] According to an embodiment, the polymeric shell comprises a material chosen in the group consisting of polyamide, polyurea, polyurethane, polyester, polyacrylate, polysiloxane, polycarbonate, polysulfonamide, polymers of urea and formaldehyde, melamine and formaldehyde, melamine and urea, or melamine and glyoxal and mixtures thereof.

[0132] According to a particular embodiment, the polymeric material is a polyamide.

[0133] According to a particular embodiment, the polyamide material is obtained from the reaction between an acyl chloride and at least one amino compound (namely at least one amino-compound A), for example ethylene diamine (EDA).

[0134] According to a particular embodiment, the polyamide material is obtained from the reaction between an acyl chloride and at least two amino compounds (namely at least one amino-compound A and at least one amino-compound B), for example L-Lysine and ethylene diamine (EDA).

[0135] According to a particular embodiment, the polyamide is obtained from the reaction between an acyl chloride and at least three amino compounds (namely at least one amino-compound A, at least one amino-compound B and at least one amino-compound C), for example L-Lysine, ethylene diamine (EDA) and diethylene triamine (DETA).

[0136] The amino-compound (A and/or B and/or C) can be chosen in the group consisting of cystamine, cystamine hydrochloride, cystine, cystine hydrochloride, cystine dialkyl ester, cystine dialkyl ester hydrochloride, a xylylene diamine, 1,2-diaminocyclohexane, 1,4-diaminocyclohexane, polyetheramines, ethylene diamine, diethylene triamine, spermine, spermidine, polyamidoamine (PAMAM), guanidine carbonate, chitosan, tris-(2-aminoethyl)amine, 3-aminopropyltriethoxysilane, 1,4 Diaminobutane, 2,2Dimethyl-1,3-propanediamine, 1,3-diaminopentane (Dytek EP diamine), 1,2 Diaminopropane, triethylenetetramine, 1,3-diaminopropane; urea; ethylene urea; aminoguanidine bicarbonate; 1-(2-aminoethyl) imidazolidin-2-one; N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine; N1-(2-Aminoethyl)-N1-dodecyl-1,2-ethanediamine; aminoethylethanolamine; N1-(3-aminopropyl) propane-1,3-diamine, polyethyleneimine, amino-acid such as L-Lysine, L-Arginine, L-Histidine, L-Tryptophane, L-Serin, L-Glutamine, L-Threonine, L-Leucine, and/or its derived oligomers and polymers, and mixtures thereof.

[0137] According to a particular embodiment, at least one of the amino-compound is an amino-acid, preferably chosen in the group consisting of L-Lysine, L-Arginine, L-Histidine, L-Tryptophane, L-Serin, L-Glutamine, L-Threonine, L-Leucine, and mixtures thereof.

[0138] According to an embodiment, the amino-compound (A and/or B and/or C) is chosen in the group consisting of a xylylene diamine, 1,2-diaminocyclohexane, 1,4-diaminocyclohexane, L-lysine, L-Lysine ethyl ester, polyetheramines (Jeffamine®), ethylene diamine, diethylene triamine, spermine, spermidine, polyamidoamine (PAMAM), guanidine carbonate, chitosan, tris-(2-aminoethyl)amine, 3-aminopropyltriethoxysilane, L-arginine, 1,4 Diaminobutane, 2,2Dimethyl-1,3-propanediamine, 1,3-diaminopentane (Dytek EP diamine), 1,2 Diaminopropane, triethylenetetramine, an amine having a disulfide bond such as cystamine, cystamine hydrochloride, cystine, cystine hydrochloride, cystine dialkyl ester, cystine dialkyl ester hydrochloride and mixtures thereof.

[0139] According to a particular embodiment, the acyl chloride has the following formula (I)
##STR00001##

wherein n is an integer varying between 1 and 8, preferably between 1 and 6, more preferably between 1 and 4, and wherein X is an (n+1)-valent C.sub.2 to C.sub.45 hydrocarbon group optionally comprising at least one group selected from (i) to (xi), more particularly selected from (i) to (vi),

##STR00002## [0140] wherein R is a hydrogen atom or an alkyl group such as a methyl or an ethyl group, preferably a hydrogen atom.

[0141] It is understood that by “ . . . hydrocarbon group . . . ” it is meant that said group consists of hydrogen and carbon atoms and can be in the form of an aliphatic hydrocarbon, i.e. linear or branched saturated hydrocarbon (e.g. alkyl group), a linear or branched unsaturated hydrocarbon (e.g. alkenyl or alkynil group), a saturated cyclic hydrocarbon (e.g. cycloalkyl) or an unsaturated cyclic hydrocarbon (e.g. cycloalkenyl or cycloalkynyl), or can be in the form of an aromatic hydrocarbon, i.e. aryl group, or can also be in the form of a mixture of said type of groups, e.g. a specific group may comprise a linear alkyl, a branched alkenyl (e.g. having one or more carbon-carbon double bonds), a (poly)cycloalkyl and an aryl moiety, unless a specific limitation to only one type is mentioned. Similarly, in all the embodiments of the invention, when a group is mentioned as being in the form of more than one type of topology (e.g. linear, cyclic or branched)

and/or being saturated or unsaturated (e.g. alkyl, aromatic or alkenyl), it is also meant a group which may comprise moieties having any one of said topologies or being saturated or unsaturated, as explained above. Similarly, in all the embodiments of the invention, when a group is mentioned as being in the form of one type of saturation or unsaturation, (e.g. alkyl), it is meant that said group can be in any type of topology (e.g. linear, cyclic or branched) or having several moieties with various topologies.

[0142] It is understood that with the term “ . . . a hydrocarbon group, optionally comprising . . . ” it is meant that said hydrocarbon group optionally comprises heteroatoms to form ether, thioether, amine, nitrile or carboxylic acid groups and derivatives (including for example esters, acids, amide). These groups can either substitute a hydrogen atom of the hydrocarbon group and thus be laterally attached to said hydrocarbon, or substitute a carbon atom (if chemically possible) of the hydrocarbon group and thus be inserted into the hydrocarbon chain or ring.

[0143] According to a particular embodiment, the acyl chloride is chosen from the group consisting of benzene-1,3,5-tricarbonyl trichloride (trimesoyl trichloride), benzene-1,2,4-tricarbonyl trichloride, benzene-1,2,4,5-tetracarbonyl tetrachloride, cyclohexane-1,3,5-tricarbonyl trichloride, isophthaloyl dichloride, diglycolyl dichloride, terephthaloyl chloride, fumaryl dichloride, adipoyl chloride, succinic dichloride, propane-1,2,3-tricarbonyl trichloride, cyclohexane-1,2,4,5-tetracarbonyl tetrachloride, 2,2'-disulfanediyl disuccinyl dichloride, 2-(2-chloro-2-oxo-ethyl) sulfanylbutanedioyl dichloride, (4-chloro-4-oxobutanoyl)-L-glutamoyl dichloride, (S)-4-((1,5-dichloro-1,5-dioxopentan-2-yl)amino)-4-oxobutanoic acid, 2,2-bis[(4-chloro-4-oxobutanoyl)oxymethyl]butyl 4-chloro-4-oxo-butanoate, [2-[2,2-bis[(4-chloro-4-oxobutanoyl)oxymethyl]butoxymethyl]-2-[(4-chloro-4-oxobutanoyl)oxymethyl]butyl]4-chloro-4-oxobutanoate, 2,2-bis[(2-chlorocarbonylbenzoyl)oxymethyl]butyl 2-chlorocarbonyl-benzoate, [2-[2,2-bis[(2-chlorocarbonylbenzoyl)oxymethyl]butoxymethyl]-2-[(2-chlorocarbonylbenzoyl)oxymethyl]butyl]2-chlorocarbonylbenzoate, 4-(2,4,5-trichlorocarbonylbenzoyl)oxybutyl 2,4,5-trichlorocarbonyl-benzoate, propane-1,2,3-triyl tris (4-chloro-4-oxobutanoate), propane-1,2-diyl bis(4-chloro-4-oxobutanoate) and mixtures thereof.

[0144] According to a particular embodiment, the acyl chloride is chosen from the group consisting of benzene-1,2,4-tricarbonyl trichloride, benzene-1,2,4,5-tetracarbonyl tetrachloride, cyclohexane-1,3,5-tricarbonyl trichloride, isophthaloyl dichloride, diglycolyl dichloride, terephthaloyl chloride, fumaryl dichloride, adipoyl dichloride, succinic dichloride, propane-1,2,3-tricarbonyl trichloride, cyclohexane-1,2,4,5-tetracarbonyl tetrachloride, 2,2'-disulfanediyl disuccinyl dichloride, 2-(2-chloro-2-oxo-ethyl) sulfanylbutanedioyl dichloride, (4-chloro-4-oxobutanoyl)-L-glutamoyl dichloride, (S)-4-((1,5-dichloro-1,5-dioxopentan-2-yl)amino)-4-oxobutanoic acid, 2,2-bis[(4-chloro-4-oxobutanoyl)oxymethyl]butyl 4-chloro-4-oxo-butanoate, [2-[2,2-bis[(4-chloro-4-oxobutanoyl)oxymethyl]butoxymethyl]-2-[(4-chloro-4-oxobutanoyl)oxymethyl]butyl]4-chloro-4-oxobutanoate, 2,2-bis[(2-chlorocarbonylbenzoyl)oxymethyl]butyl 2-chlorocarbonyl-benzoate, [2-[2,2-bis[(2-chlorocarbonylbenzoyl)oxymethyl]butoxymethyl]-2-[(2-chlorocarbonylbenzoyl)oxymethyl]butyl]2-chlorocarbonylbenzoate, 4-(2,4,5-trichlorocarbonylbenzoyl)oxybutyl 2,4,5-trichlorocarbonyl-benzoate, propane-1,2,3-triyl tris (4-chloro-4-oxobutanoate), propane-1,2-diyl bis(4-chloro-4-oxobutanoate), and mixtures thereof.

[0145] According to another particular embodiment, the acyl chloride is chosen from the group consisting of fumaryl dichloride, adipoyl dichloride, succinic dichloride, propane-1,2,3-triyl tris (4-chloro-4-oxobutanoate), propane-1,2-diyl bis(4-chloro-4-oxobutanoate), and mixtures thereof.

[0146] According to an embodiment, the acyl chloride is a mixture of acyl chlorides.

[0147] The weight ratio between acyl chloride and the hydrophobic material is preferably comprised between 0.01 and 0.09, more preferably between 0.02 and 0.07.

[0148] According to a particular embodiment, the acyl chloride is used in an amount comprised between 1.7 and 7%, preferably between 2.5 and 5% by weight based on the total weight of the hydrophobic material.

[0149] According to a particular embodiment, the protein is chosen in the group consisting of potato protein, chickpea protein, pea protein and mixtures thereof.

[0150] According to a particular embodiment, the core-shell microcapsule comprises: [0151] a core comprising a hydrophobic material, preferably a perfume oil, and [0152] a polyamide shell comprising the reaction product between one acyl chloride and at least two amino-compounds, preferably L-Lysine and ethylene diamine, wherein the polyamide shell comprises a potato protein.

[0153] According to a particular embodiment, the core-shell microcapsule comprises: [0154] a core comprising a hydrophobic material, preferably a perfume oil, and [0155] a polyamide shell comprising the reaction product between one acyl chloride and at least two amino-compounds, preferably L-Lysine and ethylene diamine, wherein the polyamide shell comprises a chickpea protein.

[0156] According to a particular embodiment, the core-shell microcapsule comprises: [0157] a core comprising a hydrophobic material, preferably a perfume oil, and [0158] a polyamide shell comprising the reaction product between one acyl chloride and at least two amino-compounds, preferably L-Lysine and ethylene diamine, wherein the polyamide shell comprises a pea protein.

[0159] The polyamide shell can comprise the reaction product between one acyl chloride and at least three amino-compounds, preferably L-Lysine, ethylene diamine and ethylene triamine.

[0160] Another object of the invention is a polyamide-based core-shell microcapsule or a polyamide-based core-shell microcapsule slurry comprising at least one microcapsule, the microcapsule comprising: [0161] a core comprising a hydrophobic material, preferably a perfume, and [0162] a polyamide-based shell comprising a reaction product of [0163] an acyl chloride in an amount comprised between 5 and 98%, preferably between 20 and 98%, more preferably between 30 and 85% w/w [0164] an amino compound A, in an amount comprised between 1% and 50% w/w, preferably between 7 and 40% w/w; [0165] optionally an amino compound B, in an amount comprised between 1% and 50% w/w, preferably between 2 and 25% w/w [0166] optionally an amino compound C, in an amount comprised between 1% and 50% w/w, preferably between 2 and 25% w/w [0167] a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof, in an amount comprised between 0.1 and 90% w/w, preferably between 0.1 and 75% w/w, more preferably between 1 and 70% w/w, based on the total weight of the shell.

According to another embodiment, the polyamide-based shell comprises a reaction product of: [0168] an acyl chloride in an amount comprised between 5 and 98%, preferably between 5 and 40%, more preferably between 5 and 30% w/w [0169] an amino compound A, in an amount comprised between 1% and 50% w/w, preferably between 7 and 40% w/w; [0170] optionally an amino compound B, in an amount comprised between 1% and 50% w/w, preferably between 2 and 25% w/w [0171] optionally an amino compound C, in an amount comprised between 1% and 50% w/w, preferably between 2 and 25% w/w [0172] a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof, in an amount comprised between 0.1 and 90% w/w, preferably between 0.1 and 75% w/w, more preferably between 1 and 70% w/w, based on the total weight of the shell.

[0173] According to an embodiment, the shell comprises the protein in an amount comprised between 1 and 80% w/w, more preferably between 10 and 75% w/w, even more preferably between 30 and 70% w/w based on the total weight of the shell.

[0174] In a particular embodiment, the shell material is a biodegradable material.

[0175] In a particular embodiment, the shell has a biodegradability of at least 40%, preferably at least 45%, 50%, 60%, 65%, 70%, 75%, 80%, 85%, 90%, 95% or 98%, within 60 days according to OECD301F.

[0176] In a particular embodiment, the core-shell microcapsule has a biodegradability of at least

40%, preferably at least 60%, preferably at least 65%, 70%, 75%, 80%, 85%, 90%, 95% or 98% within 60 days according to OECD301F.

[0177] Thereby it is understood that the core-shell microcapsule including all components, such as the core, shell and optionally coating may have a biodegradability of at least 40%, preferably at least 60%, preferably at least 65%, 70%, 75%, 80%, 85%, 90%, 95% or 98% within 60 days according to OECD301F.

[0178] In a particular embodiment, the oil core, preferably perfume oil, has a biodegradability of at least 40%, preferably at least 60%, preferably at least 65%, 70%, 75%, 80%, 85%, 90%, 95% or 98% within 60 days according to OECD301F. OECD301F is a standard test method on the biodegradability from the Organization of Economic Co-operation and Development.

[0179] A typical method for extracting the shell for measuring the biodegradability is disclosed in *Gasparini and all in Molecules* 2020, 25,718.

[0180] In a particular embodiment, the microcapsule has a stability or chemical stability of not more than 50%, preferably not more than 40%, preferably not more than 35%, preferably more than 30%. Typically, the stability or chemical stability of the microcapsules being determined as not more than 50%, preferably not more than 40%, preferably not more than 35%, preferably not more than 30%, of the perfume leaking out of the microcapsules when incorporated in a consumer product for a particular storage time and temperature, with the microcapsules being stable after 15 days storage at 37° C., more preferably after 30 days storage at 37° C. preferably in fabric softeners, liquid detergents, body washes, deodorants or antiperspirants, for at least 2 weeks storage at 40° C. in body lotions, shampoos or hair conditioners.

[0181] Furthermore, the microcapsule shows preferably a rubbing effect detectable on fresh samples, and preferably after 15 days of storage in application at 37° C., even more preferably after 30 days at 37° C.

Protein

[0182] Protein used in the present invention is a plant-protein or a plant-based protein. “Plant-protein” or “plant-based protein” are used indifferently in the present invention. The protein is chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof.

[0183] Potato proteins are typically extracted from potato tuber (*Solanum tuberosum*). According to an embodiment, the potato protein is a native potato protein and preferably comprises or consisting of patatin.

[0184] According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 10%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 20%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 30%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 40%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 50%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 60%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 70%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 80%. According to an embodiment, the solubility of the protein, preferably potato protein, is greater than 90%. The above solubilities are given in water at room temperature (typically 20° C.) and preferably at native pH.

[0185] The protein used in this invention may be native, partially or completely denatured by any suitable method. Denaturation is a process which modify the conformational structure of a protein by unfolding, i.e., it involves the disruption and possible destruction of both the secondary and tertiary structures of the protein. Indeed, denaturation implicates the breaking of many of the weak linkages, or bonds (e.g., hydrogen bonds), within a protein molecule that are responsible for the highly ordered structure of the protein in its native state. Denaturation is reversible (the proteins

can regain their native state when the denaturing influence is removed) or irreversible.

[0186] Denaturation can be brought about in various ways. Proteins can be denatured by exposure to temperature, radiation or mechanical stress including shear, changes in pH (treatment with a base or an acid), treatment with oxidizing or reducing agents, inorganic salt, certain organic solvents, chaotropic agents (i.e, compounds having a positive chaotropic value $\text{kJ Kg.sup.}-1$ mole on the Hallsworth Scale—such as guanidine salts—e.g., guanidine carbonate, guanidine hydrochloride-, urea, calcium chloride, n-butanol, ethanol, lithium perchlorate, lithium acetate, magnesium chloride, phenol, 2-propanol, sodium dodecyl sulfate, thiourea).

[0187] The protein used in this invention can also be derivatized or modified (e.g., derivatized or chemically modified). For example, the protein can be modified by covalently attaching sugars, lipids, peptides or chemical groups such as phosphates or methyl.

[0188] According to an embodiment, before use, the protein can be treated by a heat treatment (typically around 90°C.) with or without the presence of a salt (for example CaCl.sub.2) or NaCl).

Outer Coating

[0189] According to a particular embodiment of the invention, the microcapsule comprises an outer coating, wherein the outer coating comprises a coating material selected from the group consisting of a non-ionic polysaccharide, a cationic polymer, a polysuccinimide derivative (as described for instance in WO2021185724) and mixtures thereof to form an outer coating to the microcapsule.

[0190] Non-ionic polysaccharide polymers are well known to a person skilled in the art and are described for instance in WO2012/007438 page 29, lines 1 to 25 and in WO2013/026657 page 2, lines 12 to 19 and page 4, lines 3 to 12. Preferred non-ionic polysaccharides are selected from the group consisting of locust bean gum, xyloglucan, guar gum, hydroxypropyl guar, hydroxypropyl cellulose and hydroxypropyl methyl cellulose.

[0191] Cationic polymers are well known to a person skilled in the art. Preferred cationic polymers have cationic charge densities of at least 0.5 meq/g , more preferably at least about 1.5 meq/g , but also preferably less than about 7 meq/g , more preferably less than about 6.2 meq/g . The cationic charge density of the cationic polymers may be determined by the Kjeldahl method as described in the US Pharmacopoeia under chemical tests for Nitrogen determination. The preferred cationic polymers are chosen from those that contain units comprising primary, secondary, tertiary and/or quaternary amine groups that can either form part of the main polymer chain or can be borne by a side substituent directly connected thereto. The weight average (M_w) molecular weight of the cationic polymer is preferably between $10,000$ and 3.5M Dalton , more preferably between $50,000$ and 1.5M Dalton . According to a particular embodiment, one will use cationic polymers based on acrylamide, methacrylamide, N-vinylpyrrolidone, quaternized N,N-dimethylaminomethacrylate, diallyldimethylammonium chloride, quaternized vinylimidazole (3-methyl-1-vinyl-1H-imidazol-3-ium chloride), vinylpyrrolidone, acrylamidopropyltrimonium chloride, cassia

hydroxypropyltrimonium chloride, guar hydroxypropyltrimonium chloride or polygalactomannan 2-hydroxypropyltrimethylammonium chloride ether, starch hydroxypropyltrimonium chloride and cellulose hydroxypropyltrimonium chloride. Preferably copolymers shall be selected from the group consisting of polyquaternium-5, polyquaternium-6, polyquaternium-7, polyquaternium10, polyquaternium-11, polyquaternium-16, polyquaternium-22, polyquaternium-28, polyquaternium-43, polyquaternium-44, polyquaternium-46, cassia hydroxypropyltrimonium chloride, guar hydroxypropyltrimonium chloride or polygalactomannan 2-hydroxypropyltrimethylammonium chloride ether, starch hydroxypropyltrimonium chloride and cellulose hydroxypropyltrimonium chloride. As specific examples of commercially available products, one may cite Salcare® SC60 (cationic copolymer of acrylamidopropyltrimonium chloride and acrylamide, origin: BASF) or Luviquat®, such as the PQ 1 IN, FC 550 or Style (polyquaternium-11 to 68 or quaternized copolymers of vinylpyrrolidone origin: BASF), or also the Jaguar® (C.sub.13S or C17, origin Rhodia).

[0192] According to any one of the above embodiments of the invention, there is added an amount

of polymer described above comprised between about 0% and 5% w/w, or even between about 0.1% and 2% w/w, percentage being expressed on a w/w basis relative to the total weight of the slurry. It is clearly understood by a person skilled in the art that only part of said added polymers will be incorporated into/deposited on the microcapsule shell.

[0193] According to a particular embodiment, the microcapsule of the present invention comprises a mineral layer. The mineral layer preferably comprises a material chosen in the group consisting of iron oxides, iron oxyhydroxide, titanium oxides, zinc oxides, calcium carbonates, calcium phosphates, barium salt, strontium salt, magnesium salt, and mixtures thereof and mixtures thereof.

Optional Components

[0194] When microcapsules are in the form of a slurry, the microcapsule slurry can comprise auxiliary ingredients selected from the group of thickening agents/rheology modifiers, antimicrobial agents, opacity-building agents, mica particles, salt, pH stabilizers/buffering ingredients, preferably in an amount comprised between 0 and 15% by weight based on the total weight of the slurry.

[0195] According to another embodiment, the microcapsule slurry of the invention comprises additional free (i.e. non-encapsulated) perfume, preferably in an amount comprised between 5 and 50% by weight based on the total weight of the slurry.

Solid particles

[0196] Another object of the invention is a solid particle comprising: [0197] a carrier material, preferably a polymeric carrier material chosen in the group consisting of polyvinyl acetate, polyvinyl alcohol, dextrans, natural or modified starch, vegetable gums, pectins, xanthans, alginates, carragenans, cellulose derivatives and mixtures thereof, and [0198] microcapsules as defined above entrapped in said carrier material, and [0199] optionally free perfume entrapped in said carrier material.

[0200] Solid particle as defined above and microcapsule powder can be used indifferently in the present invention.

Process for Preparing a Microcapsule Slurry

[0201] Another object of the invention is a process for preparing a core-shell microcapsule slurry comprising the step of: [0202] a) Preparing an oil phase comprising a hydrophobic material, preferably a perfume to form an oil phase; [0203] b) Dispersing the oil phase obtained in step a) into a water phase to form an oil-in water emulsion; [0204] c) Performing a curing step to form microcapsules in the form of a slurry; [0205] wherein a polyfunctional monomer is added in the oil phase and/or in the water phase, and [0206] wherein a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase.

[0207] According to an embodiment, the polyfunctional monomer is chosen in the group consisting of at least one acyl chloride, a polyisocyanate, poly anhydride (such as poly maleic anhydride), polyepoxide, acrylate monomers, polyalkoxysilane, and mixtures thereof.

[0208] According to a particular embodiment, the polyfunctional monomer is a polyisocyanate having at least two isocyanate functional groups.

[0209] Suitable polyisocyanates used according to the invention can include aromatic polyisocyanate, aliphatic polyisocyanate and mixtures thereof. Said polyisocyanate comprises at least 2, preferably at least 3 but may comprise up to 6, or even only 4, isocyanate functional groups. According to a particular embodiment, a triisocyanate (3 isocyanate functional group) is used.

[0210] According to one embodiment, said polyisocyanate is an aromatic polyisocyanate.

[0211] The term "aromatic polyisocyanate" is meant here as encompassing any polyisocyanate comprising an aromatic moiety. Preferably, it comprises a phenyl, a toluyl, a xylyl, a naphthyl or a diphenyl moiety, more preferably a toluyl or a xylyl moiety. Preferred aromatic polyisocyanates are biurets, polyisocyanurates and trimethylol propane adducts of diisocyanates, more preferably

comprising one of the above-cited specific aromatic moieties. More preferably, the aromatic polyisocyanate is a polyisocyanurate of toluene diisocyanate (commercially available from Bayer under the tradename Desmodur® RC), a trimethylol propane-adduct of toluene diisocyanate (commercially available from Bayer under the tradename Desmodur® L75), a trimethylol propane-adduct of xylylene diisocyanate (commercially available from Mitsui Chemicals under the tradename Takenate® D-110N). In a most preferred embodiment, the aromatic polyisocyanate is a trimethylol propane-adduct of xylylene diisocyanate.

[0212] According to another embodiment, said polyisocyanate is an aliphatic polyisocyanate. The term “aliphatic polyisocyanate” is defined as a polyisocyanate which does not comprise any aromatic moiety. Preferred aliphatic polyisocyanates are a trimer of hexamethylene diisocyanate, a trimer of isophorone diisocyanate, a trimethylol propane-adduct of hexamethylene diisocyanate (available from Mitsui Chemicals) or a biuret of hexamethylene diisocyanate (commercially available from Bayer under the tradename Desmodur® N 100), among which a biuret of hexamethylene diisocyanate is even more preferred.

[0213] According to another embodiment, the at least one polyisocyanate is in the form of a mixture of at least one aliphatic polyisocyanate and of at least one aromatic polyisocyanate, both comprising at least two or three isocyanate functional groups, such as a mixture of a biuret of hexamethylene diisocyanate with a trimethylol propane-adduct of xylylene diisocyanate, a mixture of a biuret of hexamethylene diisocyanate with a polyisocyanurate of toluene diisocyanate and a mixture of a biuret of hexamethylene diisocyanate with a trimethylol propane-adduct of toluene diisocyanate. Most preferably, it is a mixture of a biuret of hexamethylene diisocyanate with a trimethylol propane-adduct of xylylene diisocyanate.

[0214] Preferably, when used as a mixture the molar ratio between the aliphatic polyisocyanate and the aromatic polyisocyanate is ranging from 80:20 to 10:90.

[0215] According to another embodiment, the polyfunctional monomer is an acyl chloride.

According to a particular embodiment, the process comprises the steps of: [0216] a) Preparing an oil phase comprising an acyl chloride and a hydrophobic material, preferably a perfume to form an oil phase; [0217] b) Dispersing the oil phase obtained in step a) into a water phase to form an oil-in water emulsion; [0218] c) Performing a curing step to form microcapsules in the form of a slurry; [0219] wherein at least one amino-compound is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b), and [0220] wherein a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase.

[0221] The embodiments described above for the microcapsules according to the invention also apply to the process according to the invention. This particularly applies to the hydrophobic material, the protein, the acyl chloride, the amino compound(s).

Protein

[0222] According to a particular embodiment, a protein chosen in the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase. According to a particular embodiment, the protein is added in the oil phase. When added in the oil phase, the protein can be pre-dispersed (or pre-dissolved) in an inert solvent or any inert perfumery solvent/ingredient such as benzyl benzoate, triethyl citrate, ethyl acetate, vegetable oil (such as sunflower oil), hexyl salicylate, Neobee (caprylic/capric triglyceride), isopropyl myristate, triglycerides, D-limonene, silicone oil, mineral oil, benzyl salicylate, benzyl benzoate, cyclohexyl salicylate, benzyl phenylacetate, phenylethyl phenylacetate, triacetin, ethyl citrate, methyl and ethyl salicylate, benzyl cinnamate and mixtures thereof, or can be mixed to the active ingredient, preferably comprising a perfume oil.

[0223] The protein is preferably used in an amount comprised between 0.1 and 10%, preferably

between 0.5 and 7% by weight based on the total weight of the oil phase or based of the water phase.

[0224] According to an embodiment, the protein defined in the present invention acts as a stabilizer.

[0225] However, according to an embodiment, a stabilizer can be further added in the water phase and/or the oil phase to form the emulsion. According to an embodiment, the stabilizer is a colloidal stabilizer.

[0226] By “stabilizer”, it is meant a compound capable to stabilize oil/water interface as an emulsion typically by lowering the interfacial tension between the oil phase and the water phase.

[0227] “Stabilizer” or “emulsifier” can be used indifferently in the present invention. According to an embodiment, the stabilizer is a colloidal stabilizer.

[0228] The colloidal stabilizer can be a polymeric emulsifier (standard emulsion), a surfactant, or solid particles (Pickering emulsion).

[0229] “Molecular emulsifier” and “polymeric emulsifier” are used indifferently in the present invention.

[0230] By “polymeric emulsifier”, it meant an emulsifier having both a polar group with an affinity for water (hydrophilic) and a nonpolar group with an affinity for oil (hydrophobic). The hydrophilic part will dissolve in the water phase and the hydrophobic part will dissolve in the oil phase providing a film around droplets.

[0231] By “surfactant”, it meant a non-polymeric substance with a polar and a non-polar group. According to an embodiment, the stabilizer is chosen in the group consisting of inorganic particles, polymeric emulsifier such as polysaccharides, proteins, glycoproteins, and mixtures thereof.

[0232] When the stabilizer is solid particles, it can be chosen in the group consisting of calcium phosphate, silica, silicates, titanium dioxide, aluminium oxide, zinc oxide, iron oxide, mica, kaolin, montmorillonite, laponite, bentonite, perlite, dolomite, diatomite, vermiculite, hectorite, gibbsite, illite, kaolinite, aluminosilicates, gypsum, bauxite, magnesite, talc, magnesium carbonate, calcium carbonate, diatomaceous earth and mixtures thereof. According to a particular embodiment, the stabilizer is a biopolymer.

[0233] According to a particular embodiment, the stabilizer is the polymer as defined above. By “biopolymers” it is meant biomacromolecules produced by living organisms. Biopolymers are characterized by molecular weight distributions ranging from 1,000 (1 thousand) to 1,000,000,000 (1 billion) Daltons. These macromolecules may be carbohydrates (sugar based) or proteins (amino-acid based) or a combination of both (gums) and can be linear or branched.

[0234] According to an embodiment, the colloid stabilizer is chosen in the group consisting of gum Arabic, modified starch, polyvinyl alcohol, polyvinylpyrrolidone (PVP), acrylamide copolymer, inorganic particles, protein such as soy protein, rice protein, whey protein, white egg albumin, sodium caseinate, gelatin, bovine serum albumin, hydrolyzed soy protein, hydrolyzed sericin, pseudocollagen, silk protein, sericin powder, and mixtures thereof. When added in the oil phase, the stabilizer can be pre-dispersed (or pre-dissolved) in an inert solvent or any inert perfumery solvent/ingredient such as benzyl benzoate, triethyl citrate, ethyl acetate, vegetable oil (such as sunflower oil), hexyl salicylate, Neobee (caprylic/capric triglyceride), isopropyl myristate, triglycerides, D-limonene, silicone oil, mineral oil, benzyl salicylate, benzyl benzoate, cyclohexyl salicylate, benzyl phenylacetate, phenylethyl phenylacetate, triacetin, ethyl citrate, methyl and ethyl salicylate, benzyl cinnamate and mixtures thereof, or can be mixed to the active ingredient, preferably comprising a perfume oil.

[0235] The stabilizer and acyl chloride can be premixed and can be heated at a temperature between for example 10 and 80° C. before mixing with the hydrophobic material, preferably comprising a perfume oil.

[0236] When the colloidal stabilizer is added in the water phase, it is preferably chosen in the group consisting of gum Arabic, modified starch, polyvinyl alcohol, polyvinylpyrrolidone (PVP),

acrylamide copolymer, inorganic particles, protein such as soy protein, rice protein, whey protein, white egg albumin, sodium caseinate, gelatin, bovine serum albumin, hydrolyzed soy protein, hydrolyzed sericin, Pseudocollagen, Silk protein, sericin powder, and mixtures thereof.

[0237] According to any one of the above embodiments of the present invention, the dispersion can comprise between about 0.01% and 3.0% of at least stabilizer, preferably colloidal stabilizer, percentage being expressed on a w/w basis relative to the total weight of the oil-in-water emulsion as obtained after step b). In still another aspect of the invention, the dispersion can comprise between about 0.05% and 2.0%, preferably between 0.05 and 1% of at least a stabilizer, preferably colloidal stabilizer. In still another aspect of the invention, the dispersion can comprise between about 0.1% and 1.6%, preferably between 0.1% and 0.8% by weight of at least a stabilizer, preferably colloidal stabilizer,

Acyl Chloride

[0238] The acyl chloride used in the process can be defined as it has been previously described for the microcapsules.

[0239] The weight ratio between acyl chloride and the hydrophobic material is preferably comprised between 0.01 and 0.09, more preferably between 0.02 and 0.07.

[0240] According to a particular embodiment, the acyl chloride is used in an amount comprised between 1.7 and 7%, preferably between 2.5 and 5% by weight based on the total weight of the hydrophobic material.

[0241] The acyl chloride can be dissolved (or dispersed) directly in the perfume oil or can be pre-dispersed (or pre-dissolved) in an inert solvent or any inert perfumery solvent/ingredient such as benzyl benzoate, triethyl citrate, ethyl acetate, vegetable oil (such as sunflower oil), hexyl salicylate, Neobee (caprylic/capric triglyceride), isopropyl myristate, triglycerides, D-limonene, silicone oil, mineral oil, benzyl salicylate, benzyl benzoate, cyclohexyl salicylate, benzyl phenylacetate, phenylethyl phenylacetate, triacetin, ethyl citrate, methyl and ethyl salicylate, benzyl cinnamate and mixtures thereof, before mixing with the perfume oil.

Base

[0242] According to an embodiment, the water phase comprises a base preferably chosen in the group consisting of sodium carbonate, sodium bicarbonate, sodium hydroxide, guanidine carbonate, triethanolamine and mixtures thereof.

[0243] The base can also be added in the oil-in-water emulsion.

[0244] According to a particular embodiment, the base is not an amino compound.

[0245] According to an embodiment, the water phase comprises a base preferably chosen in the group consisting of sodium carbonate, sodium bicarbonate, sodium hydroxide, and mixtures thereof.

[0246] The base can be added in an amount comprise between 0.01 and 1.5%, preferably between 0.01 and 0.7% by weight based on the total weight of the water phase.

Amino Compound(s)

[0247] According to an embodiment, at least one amino-compound (amino-compound A) is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b).

[0248] According to an embodiment, the molar ratio between the functional groups NH_2 of the at least amino compound and the functional groups COCl of the acyl chloride is comprised between 0.2 and 3, preferably from 0.5 to 2, more preferably between 0.2 and 1.

[0249] According to an embodiment, at least one additional amino-compound (amino-compound B) is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b).

[0250] According to an embodiment, at least one additional amino-compound to amino-compounds A and B (amino-compound C) is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b).

[0251] According to an embodiment, the amino-compound (A and/or B and/or C) is chosen in the group consisting of a xylylene diamine, 1,2-diaminocyclohexane, 1,4-diaminocyclohexane, L-lysine, L-Lysine ethyl ester, polyetheramines (Jeffamine®), ethylene diamine, diethylene triamine, spermine, spermidine, polyamidoamine (PAMAM), guanidine carbonate, chitosan, tris-(2-aminoethyl)amine, 3-aminopropyltriethoxysilane, L-arginine, 1,4 Diaminobutane, 2,2Dimethyl-1,3-propanediamine, 1,3-diaminopentane (Dytek EP diamine), 1,2 Diaminopropane, triethylenetetramine, an amine having a disulfide bond such as cystamine, cystamine hydrochloride, cystine, cystine hydrochloride, cystine dialkyl ester, cystine dialkyl ester hydrochloride and mixtures thereof.

[0252] According to an embodiment, the amino-compound (A and/or B and/or C) is chosen in the group consisting of cystamine, cystamine hydrochloride, cystine, cystine hydrochloride, cystine dialkyl ester, cystine dialkyl ester hydrochloride, a xylylene diamine, 1,2-diaminocyclohexane, 1,4-diaminocyclohexane, polyetheramines, ethylene diamine, diethylene triamine, spermine, spermidine, polyamidoamine (PAMAM), guanidine carbonate, chitosan, tris-(2-aminoethyl)amine, 3-aminopropyltriethoxysilane, 1,4 Diaminobutane, 2,2Dimethyl-1,3-propanediamine, 1,3-diaminopentane (Dytek EP diamine), 1,2 Diaminopropane, triethylenetetramine, 1,3-diaminopropane; urea; ethylene urea; aminoguanidine bicarbonate; 1-(2-aminoethyl) imidazolidin-2-one; N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine; N1-(2-Aminoethyl)-N1-dodecyl-1,2-ethanediamine; aminoethylethanolamine; N1-(3-aminopropyl) propane-1,3-diamine, polyethyleneimine, amino-acid such as L-Lysine, L-Arginine, L-Histidine, L-Tryptophane, L-Serin, L-Glutamine, L-Threonine, L-Leucine, and/or its derived oligomers and polymers, and mixtures thereof.

[0253] According to an embodiment, at least one amino-compound (amino-compound A) is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b).

[0254] According to an embodiment, at least one amino-compound (amino-compound A) preferably an amino-acid, more preferably L-Lysine is added in the water phase before the formation of the oil-in-water emulsion and at least one amino-compound (amino-compound B) or at least two amino-compounds (amino-compound B and amino-compound C) are added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b), wherein the amino-compound B is preferably ethylene diamine and wherein the amino-compound C is preferably diethylene triamine.

[0255] A base can also be added in the water phase and/or in the oil-in-water emulsion.

[0256] According to an embodiment, the molar ratio between the functional groups NH₂ of ethylene diamine and diethylene triamine (EDA+DETA) and the functional groups COCl of the acyl chloride is comprised between 0.2 and 3, preferably from 0.5 to 2, more preferably between 0.2 and 1.

[0257] According to a particular embodiment, a multivalent salt (such as calcium chloride, magnesium chloride, zinc chloride, iron trichloride) is added after step b), before or during step c).
Carbohydrate

[0258] According to an embodiment, a carbohydrate is added in the water phase and/or in the oil phase. According to an embodiment, by “carbohydrate” it should be understood a polymer or an oligomer having a number of units greater than 2.

[0259] According to another embodiment, the carbohydrate, the amino-compound A and the amino compound B are different components.

[0260] According to an embodiment, at least one carbohydrate is added in the oil phase and/or in the water phase.

[0261] According to an embodiment, the carbohydrate is not a polyphenol.

[0262] According to an embodiment, the carbohydrate is not a functionalized carbohydrate.

According to an embodiment, the carbohydrate is a polysaccharide.

[0263] According to an embodiment, the polysaccharide is an anionic polysaccharide. According to a particular embodiment, the polysaccharide is added in the water phase.

[0264] The polysaccharide is preferably chosen in the group consisting of anionic salt of alginic acid, preferably alginic acid sodium salt, pectin, lignin, anionic modified starch, carboxymethylcellulose and mixtures thereof.

[0265] According to a particular embodiment, the carbohydrate is an anionic salt of alginic acid, preferably alginic acid sodium salt.

[0266] "Alginic acid sodium salt" and "sodium alginate" can be used indifferently.

[0267] According to a particular embodiment, the carbohydrate is used in an amount comprised between 0.1 and 5%, preferably between 0.5 and 1.1% by weight based on the total weight of the water phase.

Multiple Microcapsules System

[0268] According to an embodiment, the microcapsules of the invention (first type of microcapsule) can be used in combination with a second type of microcapsules. Another object of the invention is a microcapsule delivery system comprising: [0269] the microcapsules of the present invention as a first type of microcapsule, and [0270] a second type of microcapsules, wherein the first type of microcapsule and the second type of microcapsules differ in their hydrophobic material and/or their wall material and/or in their coating material.

According to a particular embodiment, the microcapsule delivery system is in the form of a slurry.

[0271] The wall of the second type of microcapsules can vary. As non-limiting examples, the polymer shell of the second type of microcapsules comprises a material selected from the group consisting of polyurea, polyurethane, polyamide, polyhydroxyalkanoates, polyacrylate, polyesters, polyaminoesters, polyepoxides, polysiloxane, polycarbonate, polysulfonamide, urea formaldehyde, melamine formaldehyde resin, melamine formaldehyde resin cross-linked with polyisocyanate or aromatic polyols, melamine urea resin, melamine glyoxal resin, gelatin/gum arabic shell wall, and mixtures thereof.

[0272] The second type of microcapsule can comprises an oil-based core comprising a hydrophobic active, preferably perfume, and a composite shell comprising a first material and a second material, wherein the first material and the second material are different, the first material is a coacervate, the second material is a polymeric material. In a particular embodiment, the weight ratio between the first material and the second material is comprised between 50:50 and 99.9:0.1. In a particular embodiment, the coacervate comprises a first polyelectrolyte, preferably selected among proteins (such as gelatin), polypeptides or polysaccharides (such as chitosan), most preferably Gelatin and a second polyelectrolyte, preferably alginate salts, cellulose derivatives guar gum, pectinate salts, carrageenan, polyacrylic and methacrylic acid or xanthan gum, or yet plant gums such as acacia gum (Gum Arabic), most preferably Gum Arabic. The coacervate first material can be hardened chemically using a suitable cross-linker such as glutaraldehyde, glyoxal, formaldehyde, tannic acid or genipin or can be hardened enzymatically using an enzyme such as transglutaminase. The second polymeric material can be selected from the group consisting of polyurea, polyurethane, polyamide, polyester, polyacrylate, polysiloxane, polycarbonate, polysulfonamide, polymers of urea and formaldehyde, melamine and formaldehyde, melamine and urea, or melamine and glyoxal and mixtures thereof, preferably polyurea and/or polyurethane. The second material is preferably present in an amount less than 3 wt. %, preferably less than 1 wt. % based on the total weight of the second type of microcapsule slurry.

[0273] As non-limiting examples, the shell of the second type of microcapsules can be aminoplast-based, polyurea-based or polyurethane-based. The shell of the second type of microcapsules can also be hybrid, namely organic-inorganic such as a hybrid shell composed of at least two types of inorganic particles that are cross-linked, or yet a shell resulting from the hydrolysis and condensation reaction of a polyalkoxysilane macro-monomeric composition.

[0274] According to an aspect, the shell of the second type of microcapsules comprises an

aminoplast copolymer, such as melamine-formaldehyde or urea-formaldehyde or cross-linked melamine formaldehyde or melamine glyoxal.

[0275] According to another aspect the shell of the second type of microcapsules is polyurea-based made from, for example but not limited to isocyanate-based monomers and amine-containing crosslinkers such as guanidine carbonate and/or guanazole. Certain polyurea microcapsules comprise a polyurea wall which is the reaction product of the polymerisation between at least one polyisocyanate comprising at least two isocyanate functional groups and at least one reactant selected from the group consisting of an amine (for example a water-soluble guanidine salt and guanidine); a colloidal stabilizer or emulsifier; and an encapsulated perfume. However, the use of an amine can be omitted. According to a particular aspect, the colloidal stabilizer includes an aqueous solution of between 0.1% and 0.4% of polyvinyl alcohol, between 0.6% and 1% of a cationic copolymer of vinylpyrrolidone and of a quaternized vinylimidazol (all percentages being defined by weight relative to the total weight of the colloidal stabilizer). According to another aspect, the emulsifier is an anionic or amphiphilic biopolymer, which may be, in one aspect, chosen from the group consisting of gum Arabic, soy protein, gelatin, sodium caseinate and mixtures thereof.

[0276] According to another embodiment, the microcapsule wall material of the second type of microcapsules may comprise any suitable resin and especially including melamine, glyoxal, polyurea, polyurethane, polyamide, polyester, etc. Suitable resins include the reaction product of an aldehyde and an amine, suitable aldehydes include, formaldehyde and glyoxal. Suitable amines include melamine, urea, benzoguanamine, glycoluril, and mixtures thereof. Suitable melamines include, methylol melamine, methylated methylol melamine, imino melamine and mixtures thereof. Suitable ureas include, dimethylol urea, methylated dimethylol urea, urea-resorcinol, and mixtures thereof. Suitable materials for making may be obtained from one or more of the following companies Solutia Inc. (St Louis, Missouri U.S.A.), Cytec Industries (West Paterson, New Jersey U.S.A.), Sigma-Aldrich (St. Louis, Missouri U.S.A.).

[0277] According to another embodiment, the second type of microcapsules is a one-shell aminoplast core-shell microcapsule obtainable by a process comprising the steps of: [0278] 1) admixing a perfume oil with at least a polyisocyanate having at least two isocyanate functional groups to form an oil phase; [0279] 2) dispersing or dissolving into water an aminoplast resin and optionally a stabilizer to form a water phase; [0280] 3) preparing an oil-in-water dispersion, wherein the mean droplet size is comprised between 1 and 100 microns, by admixing the oil phase and the water phase; [0281] 4) performing a curing step to form the wall of said microcapsule; and [0282] 5) optionally drying the final dispersion to obtain the dried core-shell microcapsule.

[0283] According to an embodiment, the second type of microcapsules is a formaldehyde-free capsule. A typical process for the preparation of aminoplast formaldehyde-free microcapsules slurry comprises the steps of [0284] 1) preparing an oligomeric composition comprising the reaction product of, or obtainable by reacting together: [0285] a. a polyamine component in the form of melamine or of a mixture of melamine and at least one C.sub.1-C.sub.4 compound comprising two NH₂ functional groups; [0286] b. an aldehyde component in the form of a mixture of glyoxal, a C.sub.4-6 2,2-dialkoxy-ethanal and optionally a glyoxalate, said mixture having a molar ratio glyoxal/C.sub.4-6 2,2-dialkoxy-ethanal comprised between 1/1 and 10/1; and [0287] c. a protic acid catalyst; [0288] 2) preparing an oil-in-water dispersion, wherein the droplet size is comprised between 1 and 600 microns, and comprising: [0289] a. an oil; [0290] b. a water medium: [0291] c. at least an oligomeric composition as obtained in step 1; [0292] d. at least a cross-linker selected amongst: [0293] i. C.sub.4-C₁₂ aromatic or aliphatic di- or tri-isocyanates and their biurets, triurets, trimers, trimethylol propane-adduct and mixtures thereof; and/or [0294] ii. a di- or tri-oxiran compounds of formula: A-(oxiran-2-ylmethyl) n wherein .sub.n stands for 2 or 3 and 1 represents a C.sub.2-C.sub.6 group optionally comprising from 2 to 6 nitrogen and/or oxygen atoms; [0295] e. optionally a C.sub.1-C.sub.4 compounds comprising two NH₂ functional groups;

[0296] 3) Heating the dispersion; and [0297] 4) Cooling the dispersion.

[0298] In another particular embodiment, the second type of microcapsule comprises [0299] an oil-based core comprising a hydrophobic active, preferably perfume, [0300] optionally an inner shell made of a polymerized polyfunctional monomer; [0301] a biopolymer shell comprising a protein, wherein at least one protein is cross-linked.

[0302] According to a particular embodiment, the protein is chosen in the group consisting of milk proteins, caseinate salts such as sodium caseinate or calcium caseinate, casein, whey protein, hydrolyzed proteins, gelatins, gluten, pea protein, soy protein, silk protein and mixtures thereof, preferably sodium caseinate, most preferably sodium caseinate

[0303] According to a particular embodiment, the protein comprises sodium caseinate and a globular protein, preferably chosen in the group consisting of whey protein, beta-lactoglobulin, ovalbumine, bovine serum albumin, vegetable proteins, and mixtures thereof.

[0304] The protein is preferably a mixture of sodium caseinate and whey protein.

[0305] According to a particular embodiment, the biopolymer shell comprises a crosslinked protein chosen in the group consisting of sodium caseinate and/or whey protein.

[0306] According to a particular embodiment, the second type of microcapsules slurry comprises at least one microcapsule made of: [0307] an oil-based core comprising the hydrophobic active, preferably perfume; [0308] an inner shell made of a polymerized polyfunctional monomer; preferably a polyisocyanate having at least two isocyanate functional groups [0309] a biopolymer shell comprising a protein, wherein at least one protein is cross-linked; [0310] wherein the protein contains preferably a mixture comprising sodium caseinate and a globular protein, preferably whey protein, [0311] optionally at least an outer mineral layer.

[0312] According to an embodiment, sodium caseinate and/or whey protein is (are) cross-linked protein(s).

[0313] The weight ratio between sodium caseinate and whey protein is preferably comprised between 0.01 and 100, preferably between 0.1 and 10, more preferably between 0.2 and 5.

[0314] In another particular embodiment, the second type of microcapsules is a polyamide core-shell polyamide microcapsule comprising: [0315] an oil-based core comprising comprising a hydrophobic active, preferably perfume, and [0316] a polyamide shell comprising or being obtainable from: [0317] an acyl chloride, [0318] a first amino compound, and [0319] a second amino compound.

[0320] According to a particular embodiment, the second type of microcapsules comprises: [0321] an oil-based core comprising a hydrophobic active, preferably perfume, and [0322] a polyamide shell comprising or being obtainable from: [0323] an acyl chloride, preferably in an amount comprised between 5 and 98%, preferably between 20 and 98%, more preferably between 30 and 85% w/w [0324] a first amino compound, preferably in an amount comprised between 1% and 50% w/w, preferably between 7 and 40% w/w; [0325] a second amino compound, preferably in an amount comprised between 1% and 50% w/w, preferably between 2 and 25% w/w [0326] a stabilizer, preferably a biopolymer, preferably in an amount comprised between 0 and 90%, preferably between 0.1 and 75%, more preferably between 1 and 70%.

[0327] According to a particular embodiment, the second type of microcapsules comprises: [0328] an oil-based core comprising a hydrophobic active, preferably perfume, and [0329] a polyamide shell comprising or being obtainable from: [0330] an acyl chloride, [0331] a first amino-compound being an amino-acid, preferably chosen in the group consisting of L-Lysine, L-Arginine, L-Histidine, L-Tryptophane and/or mixtures thereof. [0332] a second amino-compound chosen in the group consisting of ethylene diamine, diethylene triamine, cystamine and/or mixtures thereof, and [0333] a biopolymer chosen in the group consisting of casein, sodium caseinate, bovin serum albumin, whey protein, and/or mixtures thereof.

[0334] According to another aspect, the shell of the second type of microcapsules is polyurea- or polyurethane-based. Examples of processes for the preparation of polyurea and polyurethane-based

microcapsule slurry are for instance described in International Patent Application Publication No. WO2007/004166, European Patent Application Publication No. EP 2300146, and European Patent Application Publication No. EP25799. Typically a process for the preparation of polyurea or polyurethane-based microcapsule slurry include the following steps: [0335] a) Dissolving at least one polyisocyanate having at least two isocyanate groups in an oil to form an oil phase; [0336] b) Preparing an aqueous solution of an emulsifier or colloidal stabilizer to form a water phase; [0337] c) Adding the oil phase to the water phase to form an oil-in-water dispersion, wherein the mean droplet size is comprised between 1 and 500 μm , preferably between 5 and 50 μm ; and [0338] d) Applying conditions sufficient to induce interfacial polymerisation and form microcapsules in form of a slurry.

Perfuming Composition and Consumer Products

[0339] The microcapsules of the invention can be used in combination with active ingredients. An object of the invention is therefore a composition comprising: [0340] (i) microcapsules or a microcapsule slurry as defined above; [0341] (ii) an active ingredient, preferably chosen in the group consisting of a cosmetic ingredient, skin caring ingredient, perfume ingredient, flavor ingredient, malodour counteracting ingredient, bactericide ingredient, fungicide ingredient, pharmaceutical or agrochemical ingredient, a sanitizing ingredient, an insect repellent or attractant, and mixtures thereof.

[0342] The capsules of the invention show a good performance in terms of stability in challenging medium.

[0343] Another object of the present invention is a perfuming composition comprising: [0344] (i) microcapsules or a microcapsule slurry as defined above, wherein the oil comprises a perfume; [0345] (ii) at least one ingredient selected from the group consisting of a perfumery carrier, a perfumery co-ingredient and mixtures thereof; [0346] (iii) optionally at least one perfumery adjuvant.

[0347] As liquid perfumery carriers one may cite, as non-limiting examples, an emulsifying system, i.e. a solvent and a surfactant system, or a solvent commonly used in perfumery. A detailed description of the nature and type of solvents commonly used in perfumery cannot be exhaustive. However, one can cite as non-limiting examples solvents such as dipropyleneglycol, diethyl phthalate, isopropyl myristate, benzyl benzoate, 2-(2-ethoxyethoxy)-1-ethanol or ethyl citrate, which are the most commonly used. For the compositions which comprise both a perfumery carrier and a perfumery co-ingredient, other suitable perfumery carriers than those previously specified, can be also ethanol, water/ethanol mixtures, limonene or other terpenes, isoparaffins such as those known under the trademark

[0348] Isopar® (origin: Exxon Chemical) or glycol ethers and glycol ether esters such as those known under the trademark Dowanol® (origin: Dow Chemical Company). By “perfumery co-ingredient” it is meant here a compound, which is used in a perfuming preparation or a composition to impart a hedonic effect and which is not a microcapsule as defined above. In other words such a co-ingredient, to be considered as being a perfuming one, must be recognized by a person skilled in the art as being able to at least impart or modify in a positive or pleasant way the odor of a composition, and not just as having an odor.

[0349] The nature and type of the perfuming co-ingredients present in the perfuming composition do not warrant a more detailed description here, which in any case would not be exhaustive, the skilled person being able to select them on the basis of his general knowledge and according to the intended use or application and the desired organoleptic effect. In general terms, these perfuming co-ingredients belong to chemical classes as varied as alcohols, lactones, aldehydes, ketones, esters, ethers, acetates, nitriles, terpenoids, nitrogenous or sulfurous heterocyclic compounds and essential oils, and said perfuming co-ingredients can be of natural or synthetic origin. Many of these co-ingredients are in any case listed in reference texts such as the book by S. Arctander, *Perfume and Flavor Chemicals*, 1969, Montclair, New Jersey, USA, or its more recent versions, or

in other works of a similar nature, as well as in the abundant patent literature in the field of perfumery. It is also understood that said co-ingredients may also be compounds known to release in a controlled manner various types of perfuming compounds. Co-ingredients may be chosen in the group consisting of 4-(dodecylthio)-4-(2,6,6-trimethyl-2-cyclohexen-1-yl)-2-butanone, 4-(dodecylthio)-4-(2,6,6-trimethyl-1-cyclohexen-1-yl)-2-butanone, trans-3-(dodecylthio)-1-(2,6,6-trimethyl-3-cyclohexen-1-yl)-1-butanone, 2-(dodecylthio) octan-4-one, 2-phenylethyl oxo (phenyl)acetate, 3,7-dimethylocta-2,6-dien-1-yl oxo (phenyl)acetate, (Z)-hex-3-en-1-yl oxo (phenyl)acetate, 3,7-dimethyl-2,6-octadien-1-yl hexadecanoate, bis(3,7-dimethylocta-2,6-dien-1-yl) succinate, (2-((2-methylundec-1-en-1-yl)oxy)ethyl)benzene, 1-methoxy-4-(3-methyl-4-phenethoxybut-3-en-1-yl)benzene, (3-methyl-4-phenethoxybut-3-en-1-yl)benzene, 1-(((Z)-hex-3-en-1-yl)oxy)-2-methylundec-1-ene, (2-((2-methylundec-1-en-1-yl)oxy)ethoxy)benzene, 2-methyl-1-(octan-3-yloxy) undec-1-ene, 1-methoxy-4-(1-phenethoxyprop-1-en-2-yl)benzene, 1-methyl-4-(1-phenethoxyprop-1-en-2-yl)benzene, 2-(1-phenethoxyprop-1-en-2-yl) naphthalene, (2-phenethoxyvinyl)benzene, 2-(1-((3,7-dimethyloct-6-en-1-yl)oxy) prop-1-en-2-yl) naphthalene, (2-((2-pentylcyclopentylidene) methoxy)ethyl)benzene, 4-allyl-2-methoxy-1-((2-methoxy-2-phenylvinyl)oxy)benzene, (2-((2-heptylcyclopentylidene) methoxy)ethyl)benzene, 1-isopropyl-4-methyl-2-((2-pentylcyclopentylidene) methoxy)benzene, 2-methoxy-1-((2-pentylcyclopentylidene) methoxy)-4-propylbenzene, 3-methoxy-4-((2-methoxy-2-phenylvinyl)oxy)benzaldehyde, 4-((2-(hexyloxy)-2-phenylvinyl)oxy)-3-methoxy benzaldehyde or a mixture thereof or a mixture thereof.

[0350] By “perfumery adjuvant” we mean here an ingredient capable of imparting additional added benefit such as a color, a particular light resistance, chemical stability, etc. A detailed description of the nature and type of adjuvant commonly used in perfuming bases cannot be exhaustive, but it has to be mentioned that said ingredients are well known to a person skilled in the art.

[0351] Preferably, the perfuming composition according to the invention comprises between 0.01 and 30% by weight of microcapsules as defined above.

[0352] The invention's microcapsules can advantageously be used in many application fields and used in consumer products. Microcapsules can be used in liquid form applicable to liquid consumer products as well as in powder form, applicable to powder consumer products.

[0353] According to a particular embodiment, the consumer product as defined above is liquid and comprises: [0354] a) from 2 to 65% by weight, relative to the total weight of the consumer product, of at least one surfactant; [0355] b) water or a water-miscible hydrophilic organic solvent; and [0356] c) a microcapsule slurry or microcapsules as defined above, [0357] d) optionally non-encapsulated perfume.

[0358] According to a particular embodiment, the consumer product as defined above is in a powder form and comprises: [0359] a) from 2 to 65% by weight, relative to the total weight of the consumer product, of at least one surfactant; [0360] b) a microcapsule powder as defined above.

[0361] c) optionally perfume powder that is different from the microcapsules defined above.

[0362] In the case of microcapsules including a perfume oil-based core, the products of the invention, can in particular be of used in perfumed consumer products such as product belonging to fine fragrance or “functional” perfumery. Functional perfumery includes in particular personal-care products including hair-care, body cleansing, skin care, hygiene-care as well as home-care products including laundry care, surface care and air care. Consequently, another object of the present invention consists of a perfumed consumer product comprising as a perfuming ingredient, the microcapsules defined above or a perfuming composition as defined above. The perfume element of said consumer product can be a combination of perfume microcapsules as defined above and free or non-encapsulated perfume, as well as other types of perfume microcapsules than those here-disclosed.

[0363] In particular a liquid consumer product comprising: [0364] a) from 2 to 65% by weight, relative to the total weight of the consumer product, of at least one surfactant; [0365] b) water or a water-miscible hydrophilic organic solvent; and [0366] c) a perfuming composition as defined

above is another object of the invention.

[0367] Also a powder consumer product comprising [0368] (a) from 2 to 65% by weight, relative to the total weight of the consumer product, of at least one surfactant; and [0369] (b) a perfuming composition as defined above is part of the invention.

[0370] The invention's microcapsules can therefore be added as such or as part of an invention's perfuming composition in a perfumed consumer product.

[0371] For the sake of clarity, it has to be mentioned that, by “perfumed consumer product” it is meant a consumer product which is expected to deliver among different benefits a perfuming effect to the surface to which it is applied (e.g. skin, hair, textile, paper, or home surface) or in the air (air-freshener, deodorizer etc.). In other words, a perfumed consumer product according to the invention is a manufactured product which comprises a functional formulation also referred to as “base”, together with benefit agents, among which an effective amount of microcapsules according to the invention.

[0372] The nature and type of the other constituents of the perfumed consumer product do not warrant a more detailed description here, which in any case would not be exhaustive, the skilled person being able to select them on the basis of his general knowledge and according to the nature and the desired effect of said product. Base formulations of consumer products in which the microcapsules of the invention can be incorporated can be found in the abundant literature relative to such products. These formulations do not warrant a detailed description here which would in any case not be exhaustive. The person skilled in the art of formulating such consumer products is perfectly able to select the suitable components on the basis of his general knowledge and of the available literature.

[0373] Non-limiting examples of suitable perfumed consumer products can be a perfume, such as a fine perfume, a cologne, an after-shave lotion, a body-splash; a fabric care product, such as a liquid or solid detergent, tablets and unit dose (single or multi-chambers), a fabric softener, a dryer sheet, a fabric refresher, an ironing water, or a bleach; a personal-care product, such as a hair-care product (e.g. a shampoo, hair conditioner, a coloring preparation or a hair spray), a cosmetic preparation (e.g. a vanishing cream, body lotion or a deodorant or antiperspirant), or a skin-care product (e.g. a perfumed soap, shower or bath mousse, body wash, oil or gel, bath salts, or a hygiene product); an air care product, such as an air freshener or a “ready to use” powdered air freshener; or a home care product, such all-purpose cleaners, liquid or power or tablet dishwashing products, toilet cleaners or products for cleaning various surfaces, for example sprays & wipes intended for the treatment/refreshment of textiles or hard surfaces (floors, tiles, stone-floors etc.); a hygiene product such as sanitary napkins, diapers, toilet paper.

[0374] Another object of the invention is a consumer product comprising: [0375] a personal care active base, and [0376] microcapsules or a microcapsule slurry as defined above or the perfuming composition as defined above, [0377] wherein the consumer product is in the form of a personal care composition.

[0378] Personal care active bases in which the microcapsules of the invention can be incorporated can be found in the abundant literature relative to such products. These formulations do not warrant a detailed description here which would in any case not be exhaustive. The person skilled in the art of formulating such consumer products is perfectly able to select the suitable components on the basis of his general knowledge and of the available literature.

[0379] The personal care composition is preferably chosen in the group consisting of a hair-care product (e.g. a shampoo, hair conditioner, a coloring preparation or a hair spray), a cosmetic preparation (e.g. a vanishing cream, body lotion or a deodorant or antiperspirant), or a skin-care product (e.g. a perfumed soap, shower or bath mousse, body wash, oil or gel, bath salts, or a hygiene product);

[0380] Another object of the invention is a consumer product comprising: [0381] a home care or a fabric care active base, and [0382] microcapsules or a microcapsule slurry as defined above or the

perfuming composition as defined above, [0383] wherein the consumer product is in the form of a home care or a fabric care composition.

[0384] Home care or fabric care active bases in which the microcapsules of the invention can be incorporated can be found in the abundant literature relative to such products. These formulations do not warrant a detailed description here which would in any case not be exhaustive. The person skilled in the art of formulating such consumer products is perfectly able to select the suitable components on the basis of his general knowledge and of the available literature.

[0385] Preferably, the consumer product comprises from 0.1 to 15 wt %, more preferably 20 between 0.2 and 5 wt % of the microcapsules of the present invention, these percentages being defined by weight relative to the total weight of the consumer product. Of course the above concentrations may be adapted according to the benefit effect desired in each product.

[0386] An object of the invention is a consumer product, preferably a home care or a fabric care consumer product comprising the microcapsules or the microcapsule slurry as defined 25 above, wherein the consumer product has a pH less than 7.

[0387] An object of the invention is a consumer product, preferably a home care or a fabric care consumer product comprising the microcapsules or the microcapsule slurry as defined above, wherein the consumer product has a pH equals or greater than 7.

[0388] For liquid consumer product mentioned below, by “active base”, it should be understood that the active base includes active materials (typically including surfactants) and water.

[0389] For solid consumer product mention below, by “active base”, it should be understood that the active base includes active materials (typically including surfactants) and auxiliary agents (such as bleaching agents, buffering agent; builders; soil release or soil suspension polymers; granulated enzyme particles, corrosion inhibitors, antifoaming, sud suppressing agents; dyes, fillers, and mixtures thereof).

Fabric Softener

[0390] An object of the invention is a consumer product in the form of a fabric softener composition comprising: [0391] a fabric softener active base; preferably comprising at least one active material chosen in the group consisting of dialkyl quaternary ammonium salts, dialkyl ester quaternary ammonium salts (esterquats), Hamburg esterquat (HEQ), TEAQ (triethanolamine quat), silicones and mixtures thereof, the active base being used preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0392] a microcapsule slurry or microcapsules as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0393] optionally free perfume oil.

Liquid Detergent

[0394] An object of the invention is a consumer product in the form of a liquid detergent composition comprising: [0395] a liquid detergent active base; preferably comprising at least one active material chosen in the group consisting of anionic surfactant such as alkylbenzenesulfonate (ABS), secondary alkyl sulfonate (SAS), primary alcohol sulfate (PAS), lauryl ether sulfate (LES), methyl ester sulfonate (MES) and nonionic surfactant such as alkyl amines, alkanolamide, fatty alcohol poly (ethylene glycol) ether, fatty alcohol ethoxylate (FAE), ethylene oxide (EO) and propylene oxide (PO) copolymers, amine oxydes, alkyl polyglucosides, alkyl polyglucosamides, the active base being used preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0396] a microcapsule slurry or microcapsules as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0397] optionally free perfume oil.

Solid Detergent

[0398] An object of the invention is a consumer product in the form of a solid detergent composition comprising: [0399] a solid detergent active base; preferably comprising at least one

active material chosen in the group consisting of anionic surfactant such as alkylbenzenesulfonate (ABS), secondary alkyl sulfonate (SAS), primary alcohol sulfate (PAS), lauryl ether sulfate (LES), methyl ester sulfonate (MES) and nonionic surfactant such as alkyl amines, alkanolamide, fatty alcohol poly (ethylene glycol) ether, fatty alcohol ethoxylate (FAE), ethylene oxide (EO) and propylene oxide (PO) copolymers, amine oxydes, alkyl polyglucosides, alkyl polyglucosamides, the active base being used preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0400] a microcapsule powder or microcapsule slurry or microcapsules as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0401] optionally free perfume oil.

Shampoo/Shower Gel

[0402] An object of the invention is a consumer product in the form of a shampoo or a shower gel composition comprising: [0403] a shampoo or a shower gel active base; preferably comprising at least one active material chosen in the group consisting of sodium alkylether sulfate, ammonium alkylether sulfates, alkylamphoacetate, cocamidopropyl betaine, cocamide MEA, alkylglucosides and aminoacid based surfactants and mixtures thereof, the active base being used preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0404] a microcapsule slurry or microcapsules as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0405] optionally free perfume oil.

Rinse-Off Conditioner

[0406] An object of the invention is a consumer product in the form of a rinse-off conditioner composition comprising: [0407] a rinse-off conditioner active base; preferably comprising at least one active material chosen in the group consisting of cetyltrimonium chloride, stearyl trimonium chloride, benzalkonium chloride, behentrimonium chloride and mixture thereof, the active base being used preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0408] a microcapsule slurry or microcapsules as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0409] optionally free perfume oil.

Solid Scent Booster

[0410] An object of the invention is a consumer product in the form of a solid scent booster composition comprising: [0411] a solid carrier, preferably chosen in the group consisting of urea, sodium chloride, sodium sulphate, sodium acetate, zeolite, sodium carbonate, sodium bicarbonate, clay, talc, calcium carbonate, magnesium sulfate, gypsum, calcium sulfate, magnesium oxide, zinc oxide, titanium dioxide, calcium chloride, potassium chloride, magnesium chloride, zinc chloride, saccharides such as sucrose, mono-, di-, and polysaccharides and derivatives such as starch, cellulose, methyl cellulose, ethyl cellulose, propyl cellulose, polyols/sugar alcohols such as sorbitol, maltitol, xylitol, erythritol, and isomalt, PEG, PVP, citric acid or any water soluble solid acid, fatty alcohols or fatty acids and mixtures thereof, [0412] a microcapsule slurry or microcapsules as defined above, in a powdered form, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0413] optionally free perfume oil.

Liquid Scent Booster

[0414] An object of the invention is a consumer product in the form of a liquid scent booster [0415] an aqueous phase, [0416] a surfactant system essentially consisting of one or more than one non-ionic surfactant, wherein the surfactant system has a mean HLB between 10 and 14, preferably chosen in the group consisting of ethoxylated aliphatic alcohols, POE/PPG (polyoxyethylene and polyoxypropylene) ethers, mono and polyglyceryl esters, sucrose ester compounds, polyoxyethylene hydroxylesters, alkyl polyglucosides, amine oxides and combinations thereof; [0417] a linker chosen in the group consisting of alcohols, salts and esters of carboxylic acids, salts

and esters of hydroxyl carboxylic acids, fatty acids, fatty acid salts, glycerol fatty acids, surfactant having an HLB less than 10 and mixtures thereof, and [0418] a microcapsule slurry or microcapsules as defined above, in the form of a slurry, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0419] optionally free perfume oil.

Hair Coloration

[0420] An object of the invention is a consumer product in the form of an oxidative hair coloring composition comprising: [0421] an oxidizing phase comprising an oxidizing agent and an alkaline phase comprising an alkakine agent, a dye precursor and a coupling compound; wherein said dye precursor and said coupling compound form an oxidative hair dye in the presence of the oxidizing agent, preferably in an amount comprised between 85 and 99.95% by weight based on the total weight of the composition, [0422] microcapsules or a microcapsule slurry as defined above, preferably in an amount comprised between 0.05 to 15 wt %, more preferably between 0.1 and 5 wt % by weight based on the total weight of the composition, [0423] optionally free perfume oil

Perfuming Composition

[0424] According to a particular embodiment, the consumer product is in the form of a perfuming [0425] 0.1 to 30%, preferably 0.1 to 20% of microcapsules or a microcapsule slurry as defined previously, [0426] 0 to 40%, preferably 3-40% of perfume, and [0427] 20-90%, preferably 40-90% of ethanol, by weight based on the total weight of the perfuming composition.

[0428] The invention will now be further described by way of examples. It will be appreciated that the invention as claimed is not intended to be limited in any way by these examples.

EXAMPLES

General protocol

[0429] A protein was optionally dispersed in an inert solvent (for example benzyl benzoate (BB) or Neobee) and was maintained under stirring at 60° C. for 30 minutes. This solution and a polyfunctional monomer (for example: Benzene-1,3,5-tricarbonyl chloride-BTC) were added to a perfume oil (25 g or 30g-see Table 1) at room temperature to form an oil phase. Oil phase was mixed with water (94 g), the latter comprising at least one amino compound (first amino compound) and optionally a base. Reaction mixture was stirred with an Ultra Turrax at 24,000 rpm for 30 s or 1 minute to afford an emulsion. At least one amino compound (second amino-compound and optionally third amino-compound) was dissolved in water (5 g) and this solution was added dropwise to the emulsion. The reaction mixture was stirred at 60° C. for 4 h to afford a white dispersion.

[0430] Alternatively, second and optionally third amino-compound(s) can be added in the water phase before the emulsification step (see capsules F2-F5).

TABLE-US-00001 TABLE 1 Perfume oil Ingredients % in oil Ethyl 2-methyl-pentanoate 3.2% Eucalyptol 7.8% 2,4-Dimethyl-3-cyclohexene-1-carbaldehyde 0.75% Aldehyde C.sub.10 0.75% Citronellyl Nitrile 4.3% Isobornyl acetate 3% 2-tert-butyl-1-cyclohexyl acetate 9.8% Citronellyl Acetate 1.3% 2-Methylundecanal 3% Diphenyloxide 0.8% Aldehyde C.sub.12 1.3% Dicyclopentadiene acetate 9.85% Ionone beta 3.3% Undecalactone gamma 18.75% Hexyl Salicylate 15.9% Benzyl Salicylate 16.2%

Example 1

Preparation of Polyamide Microcapsules (Using Potato Protein as Protein)

TABLE-US-00002 TABLE 2 Capsule A (CA) compositions Second Third First Inert Potato Acyl amino amino amino organic protein.sup.1) chloride.sup.2) compound compound Perfume compound Base Solvent CA (g) (g) (g) (g) (g) (g) (g) (g) (g) A1 1 0.88 EDA — 25 L-Lysine NaOH BB 0.25 0.36 0.1 10 A2 1 0.88 EDA DETA 25 L-Lysine — BB 0.06 0.12 1.25 10 A3 1 0.88 EDA DETA 25 L-Lysine — BB 0.06 0.12 1.25 10 A4 1 0.88 EDA DETA 25 L-Lysine — BB 0.06 0.12 1.25 10 A5 1 0.88 EDA DETA 25 L-Lysine — Neobee 0.06 0.12 1.25 10 A6 * 1 0.88 EDA DETA 25 L-Lysine — BB 0.06 0.12 1.25 10 A7 1.19 1.06 EDA — 30 L-Lysine NaOH BB 0.140 0.36 0.1

5 A8 1.19 1.06 EDA — 30 L-Lysine NaOH BB 0.180 0.36 0.1 5 A9 1.19 1.06 EDA — 30 L-Lysine NaOH BB 0.25 0.36 0.1 5 A10 1 0.88 EDA — 25 L-Lysine NaOH BB 0.105 0.36 0.1 10 A11 1 0.8 EDA — 25 L-Lysine NaOH BB 0.096 0.36 0.1 10 .sup.1) Solanic 200; Origin: AVEBE, The Netherlands .sup.2) 1,3,5-benzene tricarbonyl chloride; origin: Aldrich, Switzerland * 0.5 g of CaCl.sub.2 added before the emulsification step EDA: Ethylene diamine - origin: Aldrich, Switzerland DETA: Diethylene triamine - origin: Aldrich, Switzerland

Example 2

Preparation of Polyamide Microcapsules (Using Chickpea Protein)

TABLE-US-00003 TABLE 3 Capsule B (CB) compositions Chick Second Third First Inert pea Acyl amino amino amino organic protein.sup.1) chloride.sup.2) compound compound Perfume compound Base Solvent CB (g) (g) (g) (g) (g) (g) (g) (g) (g) B1 1 0.88 EDA DETA 25 L-Lysine — BB 0.06 0.12 1.3 10 B2 1 0.88 EDA — 25 L-Lysine NaOH BB 0.105 0.36 0.1 B3 1 0.88 EDA — 25 L-Lysine NaOH BB 0.105 0.36 0.1 10 .sup.1) ChickP G910; origin: ChickP Protein Ltd, Israel .sup.2) 1,3,5-benzene tricarbonyl chloride; origin: Aldrich, Switzerland

Example 3

Preparation of Polyamide Microcapsules (Using Pea Protein)

TABLE-US-00004 TABLE 4 Capsule C (CC) compositions Second Third First Inert Pea Acyl amino amino amino organic protein.sup.1) chloride.sup.2) compound compound Perfume compound Base Solvent CC (g) (g) (g) (g) (g) (g) (g) (g) (g) C1 1 0.88 EDA — 25 L-Lysine NaOH BB 0.252 0.36 0.1 10 C2 1 0.88 EDA DETA 25 L-Lysine — Neobee 0.06 0.12 1.3 10 C3 1 0.8 EDA — 25 L-Lysine NaOH BB 0.096 0.36 0.1 10 .sup.1) Nutralys F85F; origin: Roquette, France .sup.2) 1,3,5-benzene tricarbonyl chloride; origin: Aldrich, Switzerland

Example 4

Preparation of Polyamide Microcapsules

TABLE-US-00005 TABLE 5 Capsule D (CD) compositions Second First Inert Acyl amino amino organic Protein chloride.sup.3) compound Perfume compound Base Solvent CD (g) (g) (g) (g) (g) (g) (g) (g) (g) D1 Faba bean 0.88 EDA 25 L-Lysine NaOH BB protein.sup.1) 1 0.105 0.36 0.1 10 D2 Barley 0.88 EDA 25 L-Lysine NaOH BB protein.sup.2) 1 0.105 0.36 0.1 10 .sup.1) Vitessence Pulse 3600; origin: Ingredion, Germany .sup.2) Everpro; origin: Evergrain, United States .sup.3) 1,3,5-benzene tricarbonyl chloride; origin: Aldrich, Switzerland

Example 5

Preparation of Polyamide Microcapsules (Using Pre-Treated Potato Protein as Protein)

TABLE-US-00006 TABLE 6 Capsule E (CE) compositions Denatured Second Third First Inert potato amino amino amino organic protein BTC.sup.2) compound compound Perfume compound Solvent CE (g) (g) (g) (g) (g) (g) (g) (g) (g) E1 1 0.88 EDA DETA 25 L-Lysine BB 0.12 0.21 1.3 10

Denaturation Process:

[0431] Solution of protein at 2% is made and NaCl is added at a concentration 100 mmol/l. The solution is heated at 90° C. for 90 min. Once cooled down, the pH of the solution is adjusted at 9.5 with NaOH 1M. This solution is then freeze dried (the solution can also be spray-dried).

Example 6

Preparation of Polyamide Microcapsules

TABLE-US-00007 TABLE 7 Capsule F (CF) compositions Second Third First Inert Potato amino amino amino organic protein.sup.1) BTC.sup.2) compound compound Perfume compound Base Solvent Salt** CF (g) (g) (g) (g) (g) (g) (g) (g) (g) F1 1 0.88 EDA DETA 25 L-Lysine — BB 0.5 0.12 0.21 1.3 10 F2* 1 0.88 CYS HCl — 25 L-Lysine NaOH BB 0.5 0.25 0.7 0.11 10 F3* 1 0.75 CYS HCl — 25 L-Lysine NaOH — 0.5 0.25 0.7 0.11 F4* 1 0.88 CYS HCl — 25 L-Lysine NaOH BB 0.5 0.35 0.7 0.11 10 F5* 1 0.88 EDA — 25 L-Lysine NaOH BB 0.5 0.105 0.7 0.11 10

*amines were added before the emulsification step **CaCl.sub.2 added before the emulsification step CYS HCL: Cystamine HCl, origin: Aldrich, Switzerland

Example 7

Stability Performance

[0432] Microcapsules of the present invention are dispersed in a fabric softener composition described in Table 8 to obtain a concentration of encapsulated perfume oil at 0.116%.

TABLE-US-00008 TABLE 8 Fabric conditioner composition Product Wt % Stepantex VL 90A
8.88 Calcium Chloride Sol. 10% 0.36 Proxel GXL 0.04 Perfume 1.00 Water 89.72 TOTAL 100
Protocol:

Sample Extraction:

[0433] The internal standard (ISTD) used for quantification is Ethyl Dodecanoate. 2 g of samples were weighed in triplicates in a 20 ml bottle flask and extracted with 10 mL of a 9/1 Isooctane/Diethyl Ether solution containing 5 mg/L ISTD. Samples are then shaken using Turbulat (1 hour; speed=52 rpm) and then allowed to stand for 15-30 min until complete decantation. The top of the organic layer is sampled with a 2 mL syringe and filtered in a GC vial through a 0.20 µm PTFE filter. The samples extractions were done in triplicate.

Analysis Conditions:

[0434] Analysis was performed on gas chromatography with a 7890 B Agilent instrument coupled with a 5977B MS detector. The instrument is fitted with a Pneumatic Control Module to ensure a backflush system and two 15 m×250 µm×0.25 µm DB-1 MS columns. Helium was used as carrier gas and the inlet temperature and pressure were 250° C. and 10.3 psi. A split mode was configured with a 20:1 split ratio and a 20 mL/min split flow and the gas saver was activated after 2 min as a flow rate of 15 mL/min. The oven program was 50° C. for 5 min, 15° C./min until 230° C. and 230° C. for 1 min and achieved with a 4 min post run backflush; then the column flow rate to MSD was 3.45 mL/min and -3.05 mL/min to inlet with aux pressure of 30 psi. The MS temperature were respectively 150° C. and 230° C. for the quadrupole and the ion source, and the scan range from 25 to 450 m/z with a solvent delay of 4 min.

Calibration:

[0435] Samples were quantified with standard curve; calibration and validation points were prepared in 9/1 Isooctane/Diethyl Ether solution containing 5 mg/L ISTD (first method).

[0436] A second calibration was prepared in softener base and extracted following the same protocol than the samples to compare and check the results obtained with the first method.

TABLE-US-00009 TABLE 9 Stability (Perfume Leakage at 37° C. - 3 days/1 month) Sample 3
days 1 month A1 13 23 A2 17 23 A3 13 23 A4 18 25 A5 19 27 A6 12 22 B1 18 30 C1 18 30 C2 16
25 D1 36 NM* D2 37 NM* E1 15 26 F1 11 19 F2 20 27 F3 22 27 F4 9 20 *not measured

[0437] One can conclude that the microcapsules of the present invention show good stability in challenging bases.

Example 8

Biodegradability of Microcapsules According to the Invention

[0438] Shell extraction (following method disclosed in *Gasparini and all in Molecules* 2020, 25,718) The water phase of the microcapsule slurry was removed by vacuum filtration over a gooch filter crucible (porosity 4) and the powder was dried. The recovered solid was grinded using a crusher IKA tube-mill control for 30 sec. The resulting paste (fragrance oil+polymeric shells) was suspended in 300 mL of Ethyl acetate and the mixture was stirred for 1 h at room temperature. The solid was collected by filtration under vacuum over a gooch filter crucible (porosity 4). This extraction step was repeated 5 times to remove the maximum of fragrance oil from the shells. The powder was dried under vacuum (10 mBar) at 50° C. until the weight of the polymer, monitored by gravimetry, was constant. The resulting powder was grinded using a crusher IKA tube-mill control for 1 min 30 sec, suspended in Di water (0.5% w/w) and stirred at 300 RPM for 24H at RT. The water was removed by filtration under vacuum over a gooch filter crucible (porosity 4) and the powder was dried at RT for 2.5 days and then under vacuum (10 mBar) at 50° C. overnight. Finally, the obtained powder was grinded using a crusher IKA tube-mill control for 1 min and 30 sec, and extracted an additional five times with ethyl acetate as described before. The final powder was

4.00% ether of Lauryl Alcohol.sup.2) alkyl polyglucoside C8- 8.30% 7.7% C10.sup.3) Deceth-3.sup.1) 1.50% Lauryl lactate 1% Lauric acid 1.5% 1.60% Glyceryl Caprylate 3.00% 3.00% Fragrance 3.00% 3.0% 3.00% 3.00% 3.00% 0% .sup.1)Deceth-8; trademark and origin: KLK Oleo .sup.2)Laureth-9;; trademark and origin .sup.3)Plantacare 2000UP; trademark and origin: BASF

[0446] Different ringing gel compositions are prepared (compositions 1-6) according to the following protocol.

[0447] In a first step, the aqueous phase (water), the solvent (propylene glycol) if present and surfactants are mixed together at room temperature under agitation with magnetic stirrer at 300 rpm for 5 min.

[0448] In a second step, the linker is dissolved in the hydrophobic active ingredient (fragrance) at room temperature under agitation with magnetic stirrer at 300 rpm. The resulting mixture is mixed for 5 min.

[0449] Then, the aqueous phase and the oil phase are mixed together at room temperature for 5 min leading to the formation of a transparent or opalescent ringing gel.

Example 11

Liquid Detergent Composition

[0450] A sufficient amount of exemplified microcapsules is weighed and mixed in a liquid detergent to add the equivalent of 0.2% perfume.

TABLE-US-00013 TABLE 13 Liquid detergent composition Concentration Ingredients [wt %]
Sodium C.sub.14-17 Alkyl Sec Sulfonate.sup.1) 7 Fatty acids, C.sub.12-18 and C.sub.18-unsaturated.sup.2) 7.5 C.sub.12/14 fatty alcohol polyglycol ether with 7 mol EO.sup.3) 17
Triethanolamine 7.5 Propylene Glycol 11 Citric acid 6.5 Potassium Hydroxyde 9.5 Properase L.sup.4) 0.2 Puradax EG L.sup.4) 0.2 Purastar ST L.sup.4) 0.2 Acrylates/Steareth-20 Methacrylate structuring 6 Crosspolymer.sup.5) Deionized Water 27.4 .sup.1)Hostapur SAS 60; Origin: Clariant .sup.2)Edenor K 12-18; Origin: Cognis .sup.3)Genapol LA 070; Origin: Clariant .sup.4)Origin: Genencor International .sup.5)Aculyn 88; Origin: Dow Chemical

Example 12

Unit Dose Formulation

[0451] A sufficient amount of exemplified microcapsules is weighed and mixed in a unit dose formulation to add the equivalent of 0.2% perfume.

[0452] The unit dose formulation can be contained in a PVOH (polyvinyl alcohol) film.

TABLE-US-00014 TABLE 14 Unit dose composition Concentration Ingredients [wt %] C12-C14 alkyl poly ethoxylate 15 C12-C14 alkyl poly ethoxylate sulfate 9.5 Mono Ethanol Amine salt Linear Alkylbenzene sulfonic acid 17 Citric Acid 0.5 C12-C18 Fatty Acid 17 Enzymes 1.2 Fluorescent brightener 0.3 1,2 propanediol 12 Glycerol 9 Sodium Hydroxide 1 Mono Ethanol Amine 6 PDMS 2.5 Potassium sulphite 0.2 Water 8.8 Total 100

Example 13

Powder Detergent Composition

[0453] A sufficient amount of exemplified microcapsules is weighed and mixed in a powder detergent composition to add the equivalent of 0.2% perfume.

TABLE-US-00015 TABLE 15 Powder detergent composition Ingredients Part Anionic (Linear Alkyl Benzene 20% Sulphonates) Nonionics (Alcohol Ethoxylates (5-9 6% ethylene oxide) Builders (zeolites, sodium carbonate) 25% Silicates 6% Sodium Sulphate 35% Others (Enzymes, Polymers, Bleach) 7.5% Spray-dried granule powder A-E 0.5%

Example 14

Concentrated all Purpose Cleaner Composition

[0454] A sufficient amount of exemplified microcapsules is weighed and mixed in a concentrated all-purpose cleaner composition to add the equivalent of 0.2% perfume.

TABLE-US-00016 TABLE 16 concentrated all-purpose cleaner composition Amount Ingredients

(% wt) Function Ethoxylated Alcohol (C9-C11, 8EO) .sup.(1) 20 Non-ionic surfactant Sodium Dodecyl Benzene Sulfonate .sup.(2) 16 Anionic surfactant Sodium Cumene Sulfonate .sup.(3) 8 Hydrotrope Methyl chloro isothiazolinone Methyl 0.8% preservative isothiazolinone 3.3:1 .sup.(4) Water 55.9 solvent .sup.(1) Neodol 91-8 ®; trademark and origin: Shell Chemical .sup.(2) Biosoft D-40 ®; trademark and origin: Stepan Company .sup.(3) Stepanate SCS ®; trademark and origin: Stepan Company .sup.(4) Kathon CG ®; trademark and origin: Dow Chemical Company All ingredients are mixed together and then the mixture was diluted with water to 100%.

Example 15

Solid Scent Booster Composition

[0455] The following compositions are prepared.

TABLE-US-00017 TABLE 17 Salt-based solid scent booster compositions

Ingredients	Part
Sodium chloride	95
Spray-dried granule powder A-E	5

TABLE-US-00018 TABLE 18 Urea-based solid scent booster compositions

Ingredients	Part
Urea (beads)	94
Spray-dried granule powder A-E	8
Bentonite	3
Perfume	3

Example 16

Shampoo Composition

[0456] A sufficient amount of exemplified microcapsules is weighed and mixed in a shampoo composition to add the equivalent of 0.2% perfume.

TABLE-US-00019 TABLE 19 Shampoo composition

Concentration	Ingredients [wt %]
A	Water deionized 44.4
	Polyquaternium-10 .sup.(1) 0.3
	Glycerin 85% .sup.(2) 1
	DMDM Hydantoin .sup.(3) 0.2
B	Sodium Laureth Sulfate .sup.(4) 28
	Cocamidopropyl Betaine .sup.(5) 3.2
	Disodium Cocoamphodiacetate .sup.(6) 4
	Ethoxy (20) Stearyl Alcohol .sup.(6) 1
C	Sodium Laureth Sulfate .sup.(4) 3
	Glyceryl Laureate .sup.(7) 0.2
D	Water deionized 1
	Sodium Methylparaben .sup.(8) 0.1
E	Sodium Chloride 10% aqueous sol. 15
	Citric acid 10% aqueous sol. till pH 5.5-6 q.s.
	Perfume 0.5
TOTAL: 100 .sup.(1)	Ucare Polymer JR-400, Noveon .sup.(2)
	Schweizerhall .sup.(3)
	Glydant, Lonza .sup.(4)
	Texapon NSO IS, Cognis .sup.(5)
	Tego Betain F 50, Evonik .sup.(6)
	Amphotensid GB 2009, Zschimmer & Schwarz .sup.(7)
	Monomuls 90 L-12, Gruenau .sup.(8)
	Nipagin Monosodium, NIPA

[0457] Polyquaternium-10 is dispersed in water. The remaining ingredients of phase A are mixed separately by addition of one after the other while mixing well after each adjunction. Then this pre-mix is added to the Polyquaternium-10 dispersion and was mixed for 5 min. Then Phase B and the premixed Phase C (heat to melt Monomuls 90L-12 in Texapon NSO IS) are added. The mixture is mixed well. Then, Phase D and Phase E are added while agitating. The pH was adjusted with citric acid solution till pH: 5.5-6.0.

Example 17

Shampoo Composition

[0458] A sufficient amount of exemplified microcapsules is weighed and mixed in a shampoo composition to add the equivalent of 0.2% perfume.

TABLE-US-00020 TABLE 20 Shampoo composition

Concentration	Ingredients [wt %]
A	Water deionized 45.97
	Tetrasodium EDTA .sup.(1) 0.05
	Guar Hydroxypropyltrimonium Chloride .sup.(2) 0.05
	Polyquaternium-10 .sup.(3) 0.075
B	NaOH 10% aqueous sol. 0.3
C	Ammonium Lauryl Sulfate .sup.(4) 34
	Ammonium Laureth Sulfate .sup.(5) 9.25
	Cocamidopropyl Betaine .sup.(6) 2
	Dimethicone (&) C12-13 Pareth-4 (&) C12-13 2.5
	Pareth-23 (&) Salicylic Acid .sup.(7) D
	Cetyl Alcohol .sup.(8) 1.2
	Cocamide MEA .sup.(9) 1.5
	Glycol Distearate .sup.(10) 2
E	Methylchloroisothiazolinone & 0.1
	Methylisothiazolinone .sup.(11) D-Panthenol 75% .sup.(12) 0.1
	Water deionized 0.3
F	Sodium Chloride 25% aqueous sol. 0.6
TOTAL: 100 .sup.(1)	EDETA B Powder, BASF .sup.(2)
	Jaguar C14 S, Rhodia .sup.(3)
	Ucare Polymer JR-400, Noveon .sup.(4)
	Sulfetal LA B-E, Zschimmer & Schwarz .sup.(5)
	Zetesol LA, Zschimmer & Schwarz .sup.(6)
	Tego Betain F 50, Evonik .sup.(7)
	Xiameter MEM-1691, Dow Corning .sup.(8)
	Lanette 16, BASF .sup.(9)
	Comperlan 100, Cognis .sup.(10)
	Cutina AGS, Cognis .sup.(11)
	Kathon CG, Rohm & Haas .sup.(12)
	D-Panthenol, Roche

[0459] A premix comprising Guar Hydroxypropyltrimonium Chloride and Polyquaternium-10 are

added to water and Tetrasodium EDTA while mixing. When the mixture is homogeneous, NaOH is added. Then, Phase C ingredients are added and the mixture was heat to 75° C. Phase 5 D ingredients are added and mixed till homogeneous. The heating is stopped and temperature of the mixture is decreased to RT. At 45° C., ingredients of Phase E while mixing final viscosity is adjusted with 25% NaCl solution and pH of 5.5-6 is adjusted with 10% NaOH solution.

Example 18

Rinse-Off Hair Composition

[0460] A sufficient amount of exemplified microcapsules is weighed and mixed in a rinse-off composition to add the equivalent of 0.2% perfume.

TABLE-US-00021 TABLE 21 rinse-off composition

Concentration	Ingredients [wt %]
A	Water deionized 81.8
B	Behentrimonium Chloride .sup.1) 2.5
C	Hydroxyethylcellulose .sup.2) 1.5
D	Cetearyl Alcohol .sup.3) 4
E	Glyceryl Stearate (and) PEG-100 Stearate .sup.4) 2
F	Behentrimonium Methosulfate (and) Cetyl alcohol 4 (and) Butylene Glycol .sup.5) Ethoxy (20) Stearyl Alcohol .sup.6) 1
G	Amodimethicone (and) Trideceth-12 (and) 3 Cetrimonium Chloride .sup.7) Chlorhexidine Digluconate .sup.8) 20% aqueous solution 0.2
H	Citric acid 10% aqueous sol. till pH 3.5-4 q.s. TOTAL: 100 .sup.1) Genamin KDMP, Clariant .sup.2) Tylose H10 Y G4, Shin Etsu .sup.3) Lanette O, BASF .sup.4) Arlacel 165, Croda .sup.5) Incroquat Behenyl TMS-50-PA- (MH), Croda .sup.6) Brij S20, Croda .sup.7) Xiameter MEM-949, Dow Corning .sup.8) Alfa Aesar

[0461] Ingredients of Phase A are mixed until an uniform mixture was obtained. Tylose is allowed to completely dissolve. Then the mixture is heated up to 70-75° C. Ingredients of Phase B are combined and melted at 70-75° C. Then ingredients of Phase B are added to Phase A with good agitation and the mixing is continued until cooled down to 60° C. Then, ingredients of Phase C are added while agitating and keeping mixing until the mixture cooled down to 40° C. The pH is adjusted with citric acid solution till pH: 3.5-4.0.

Example 19

Antiperspirant Spray Anhydrous Composition

[0462] A sufficient amount of exemplified microcapsules is weighed and mixed in an antiperspirant spray anhydrous composition to add the equivalent of 0.2% perfume.

TABLE-US-00022 TABLE 22 antiperspirant spray anhydrous composition

Ingredient	Amount (wt %)
Cyclomethicone.sup.1)	53.51
Isopropyl miristate	9.04
Silica.sup.2)	1.03
Quaternium-18-Hectorite.sup.3)	3.36
Aluminium Chlorohydrate.sup.4)	33.06
.sup.1)Dow Corning ® 345 Fluid; trademark and origin: Dow Corning .sup.2)Aerosil ® 200; trademark and origin: Evonik .sup.3)Bentone ® 38; trademark and origin: Elementis Specialities .sup.4)Micro Dry Ultrafine; origin: Reheis	

[0463] Using a high speed stirrer, Silica and Quaternium-18-Hectorite are added to the Isopropyl miristate and Cyclomethicone mixture. Once completely swollen, Aluminium Chlorohydrate is added portion wise under stirring until the mixture was homogeneous and without lumps. The aerosol cans are filled with 25% Suspension of the suspension and 75% of Propane/Butane (2,5 bar).

Example 20

Antiperspirant Spray Emulsion Composition

[0464] A sufficient amount of exemplified microcapsules is weighed and mixed in antiperspirant spray emulsion composition to add the equivalent of 0.2% perfume.

TABLE-US-00023 TABLE 23 antiperspirant spray emulsion composition

Amount	Ingredient (wt %)
Polysorbate 65.sup.1)	(Part A) 0.95
Polyglyceryl-2 dipolyhydroxystearate.sup.2)	1.05 (Part A)
Cetyl PEG/PPG-10/1 Dimethicone.sup.3)	2.75 (Part A)
Cyclomethicone.sup.4)	(Part A) 16.4
Isopropylisostearate.sup.5)	(Part A) 4.5
Phenoxyethanol.sup.6)	(Part A) 0.5
Ethylhexylglycerin.sup.7)	(Part A) 0.2
C12-15 Alkyl Benzoate.sup.8)	(Part A) 5.65
Silica Silylate.sup.9)	(Part A) 0.1
Sodium Methylparaben.sup.10)	(Part B) 0.1
Aluminium Chlorohydrate.sup.11)	(Part B) 20
Water (Part B)	44.47
Fragrance (Part C)	3.33 .sup.1)Tween 65;

trademark and origin: CRODA .sup.2)Dehymuls PGPH; trademark and origin: BASF .sup.3)Abil EM-90; trademark and origin: BASF .sup.4)Dow Corning 345 fluid; trademark and origin: Dow Corning .sup.5)Crodamol ipis; trademark and origin: CRODA .sup.6)Phenoxyethanol; trademark and origin: LANXESS .sup.7)Sensiva sc 50; trademark and origin: KRAFT .sup.8)Tegosoft TN; trademark and origin: Evonik .sup.9)Aerosil R 812; trademark and origin: Evonik .sup.10)Nipagin mna; trademark and origin: CLARIANT .sup.11)Locron L; trademark and origin: CLARIANT [0465] The ingredients of Part A and Part B are weighted separately. Ingredients of Part A are heated up to 60° C. and ingredients of Part B are heated to 55° C. Ingredients of Part B are poured small parts while continuous stirring into A. Mixture were stirred well until the room temperature was reached. Then, ingredients of part C are added. The emulsion is mixed and is introduced into the aerosol cans. The propellant is crimped and added. [0466] Aerosol filling: 30% Emulsion: 70% Propane/Butane 2,5 bar

Example 21

Deodorant Spray Composition

[0467] A sufficient amount of exemplified microcapsules is weighed and mixed in antiperspirant deodorant spray composition to add the equivalent of 0.2% perfume.

TABLE-US-00024 TABLE 24 deodorant spray composition

Amount	Ingredient (wt %)
95%	Ethanol
90.65	Triclosan. ^{sup.1)}
0.26	Isopropyl miristate
9.09	^{sup.1)} Irgasan ® DP 300; trademark and origin: BASF

[0468] All the ingredients according to the sequence of the Table 24 are mixed and dissolved. Then the aerosol cans are filled, crimp and the propellant is added (Aerosol filling: 40% active solution 60% Propane/Butane 2.5 bar).

Example 22

Antiperspirant Roll-on Emulsion Composition

[0469] A sufficient amount of exemplified microcapsules is weighed and mixed in antiperspirant roll-on emulsion composition to add the equivalent of 0.2% perfume.

TABLE-US-00025 TABLE 25 antiperspirant roll-on emulsion composition

Amount	Ingredient (wt %)
Steareth-2. ^{sup.1)}	(Part A) 3.25
Steareth-21. ^{sup.2)}	(Part A) 0.75
PPG-15 Stearyl Ether. ^{sup.3)}	(Part A) 4
WATER deionised (Part B)	51
Aluminum Chlorohydrate 50% 40 aqueous solution. ^{sup.4)}	(Part C)
Fragrance (Part D)	1
^{sup.1)} BRIJ 72; origin: ICI	^{sup.2)} BRIJ 721; origin: ICI
^{sup.3)} ARLAMOL E; origin: UNIQEMA-CRODA	^{sup.4)} LOCRON L; origin: CLARIAN

[0470] Part A and B are heated separately to 75° C.; Part A is added to part B under stirring and the mixture is homogenized for 10 minutes. Then, the mixture is cooled down under stirring; and part C is slowly added when the mixture reached 45° C. and part D when the mixture reached at 35° C. while stirring. Then the mixture is cooled down to RT.

Example 23

Antiperspirant Roll-on Composition

[0471] A sufficient amount of exemplified microcapsules is weighed and mixed in antiperspirant roll-on composition to add the equivalent of 0.2% perfume.

TABLE-US-00026 TABLE 26 antiperspirant roll-on composition

Ingredient	QUANTITY
Water (Part A)	45
Aluminum Chlorohydrate 50% aqueous 20 solution. ^{sup.1)}	(Part B)
Alcohol Denat. (Ethanol 96%) (Part B)	30
Cetareth-12. ^{sup.2)}	(Part C) 2
Cetareth-30. ^{sup.3)}	(Part C) 2
Fragrance (Part D)	1
^{sup.1)} LOCRON L; origin: CLARIANT	^{sup.2)} EUMULGIN B-1; origin: BASF
^{sup.3)} EUMULGIN B-3; origin: BASF	

[0472] The ingredients of part B are mixed in the vessel then ingredient of part A is added. Then dissolved part C in part A and B. With perfume, 1 part of Cremophor RH40 for 1 part of perfume is added while mixing well

Example 24

Antiperspirant Roll-on Composition

[0473] A sufficient amount of exemplified microcapsules is weighed and mixed in antiperspirant

roll-on emulsion composition to add the equivalent of 0.2% perfume.

TABLE-US-00027 TABLE 27 antiperspirant roll-on emulsion composition

Amount	Ingredient (wt %)
50.51	Water (Part A)
0.71	Hydroxyethylcellulose.sup.1) (Part A)
40.40	Ethanol 95% (Part B)
5.05	1,2-Propylene Glycol (Part B)
0.30	Triclosan.sup.2) (Part B)
3.03	PEG-40 Hydrogenated castor oil.sup.3) (Part C)

.sup.1)Natrosol ® 250 H; trademark and origin: Ashland .sup.2)Irgasan ® DP 300; trademark and origin: BASF .sup.3)Cremophor ® RH 40; trademark and origin: BASF [0474] Part A is prepared by sprinkling little by little the Hydroxyethylcellulose in the water whilst rapidly stirring with the turbine. Stirring is continued until the Hydroxyethylcellulose is entirely swollen and giving a limpid gel. Then, Part B is poured little by little in Part A whilst continuing stirring until the whole is homogeneous. Part C is added.

Example 25

Deodorant Pump without Alcohol Formulation

[0475] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00028 TABLE 28 deodorant composition

Amount	Ingredients (wt %)
5	C12-15 Alkyl Lactate.sup.1)
91.6	Dimethicone.sup.2)
1	Cetyl Lactate.sup.3)
0.8	Octyldodecanol.sup.4)
0.1	Triclosan.sup.5)
1.5	PERFUME .sup.1)

Ceraphyl 41; trademark and origin ASHLAND .sup.2)DOW CORNING 200 FLUID 0.65 cs; trademark and origin DOW CORNING CORPORATION .sup.3)Ceraphyl 28; trademark and origin ASHLAND .sup.4)Eutanol G; trademark and origin BASF .sup.5)Irgasan ® DP 300; trademark and origin: BASF

[0476] All the ingredients are mixed according to the sequence of the table and the mixture is heated slightly to dissolve the Cetyl Lactate.

Example 26

Deodorant Pump with Alcohol Formulation

[0477] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00029 TABLE 29 deodorant composition

Amount	Ingredients (wt %)
60	Ethyl Alcohol (Part A)
35.6	PEG-6 Caprylic/Capric Glycerides.sup.1) (Part A)
2	Water (Part A)
0.4	PEG-40 Hydrogenated Castor Oil.sup.2) (Part B)
2	PERFUME (Part B) .sup.1)

Softigen 767; trademark and origin CRODA .sup.2)Cremophor ® RH 40; trademark and origin: BASF

[0478] Ingredients from Part B are mixed together. Ingredients of Part A are dissolved according to the sequence of the Table and are poured into part B.

Example 27

Talc Formulation

[0479] A sufficient amount of granules A-E is weighed and mixed in introduced in a standard talc base: 100% talc, very slight characteristic odor, white powder, origin: LUZENAC to add the equivalent of 0.2% perfume.

Example 28

Shower-Gel Reference

[0480] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00030 TABLE 30 shower gel composition

Amount	Ingredients (% wt)	Function
49.350	WATER deionized	
0.050	Solvent Tetrasodium EDTA .sup.1)	Chelating agent
6.000	Acrylates Copolymer.sup.2)	Thickener
35.000	Sodium C12-C15 Pareth Sulfate .sup.3)	Surfactant
1.000	Sodium Hydroxide 20% pH adjuster aqueous solution	
8.000	Cocamidopropyl Betaine.sup.4)	Surfactant
0.100	Methylchloroisothiazolinone	Preservative
0.500	Methylisothiazolinone.sup.5)	

Citric Acid (40%) pH adjuster .sup.1) EDETA B POWDER; trademark and origin: BASF .sup.2)CARBOPOL AQUA SF-1 POLYMER; trademark and origin: NOVEON .sup.3) ZETESOL AO 328 U; trademark and origin: ZSCHIMMER & SCHWARZ .sup.4)TEGO-BETAIN F 50; trademark and origin: GOLDSCHMIDT .sup.5)KATHON CG; trademark and origin: ROHM &

HASS

[0481] Ingredients are mixed, pH is adjusted to 6-6.3 (Viscosity: 4500cPo+/-1500cPo (Brookfield RV/Spindle #4/20 RPM)).

Example 29

Shower-Gel Composition

[0482] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00031 TABLE 31 shower gel composition

Amount	Ingredients (% wt)	Function
52.40	WATER deionized	Solvent
0.10	Tetrasodium EDTA .sup.1)	Chelating agent
0.50	Sodium Benzoate	Preservative
2.00	Propylene Glycol	Solvent
35.00	Sodium C12-C15 Pareth Sulfate .sup.2)	Surfactant
8.00	Cocamidopropyl Betaine.sup.3)	Surfactant
0.20	Polyquaternium-7.sup.4)	Conditioning agent
1.00	Citric Acid (40%)	pH adjuster
0.80	Sodium Chloride	Viscosity adjuster

.sup.1) EDETA B POWDER; trademark and origin: BASF .sup.2) ZETESOL AO 328 U; trademark and origin: ZSCHIMMER & SCHWARZ .sup.3)TEGO-BETAIN F 50; trademark and origin: GOLDSCHMIDT .sup.4)MERQUAT 550; trademark and origin: LUBRIZOL

[0483] Ingredients are mixed, pH is adjusted to 4.5 (Viscosity: 3000cPo+/-1500cPo (Brookfield RV/Spindle #4/20 RPM)).

Example 30

Shower-Gel Composition

[0484] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00032 TABLE 32 shower gel composition

Amount	Ingredients (% wt)	Function
50.950	WATER deionized	Solvent
0.050	Tetrasodium EDTA .sup.1)	Chelating agent
0.500	Sodium Benzoate	Preservative
3.500	Glycerin 86%	Solvent
27.000	Sodium Laureth Sulfate .sup.2)	Surfactant
1.000	Polyquaternium-7.sup.3)	Conditioning Agent
6.000	Coco-Betaine.sup.4)	Surfactant
1.000	PEG-120 Methyl Glucose	Thickener
1.000	trioleate.sup.5)	Citric Acid (40%)
1.000	pH adjuster	Glycol Distearate & Laureth-4 & 3.000
	Pearlizing Cocamidopropyl Betaine.sup.6)	agent
5.000	Sodium Chloride 20%	Viscosity adjuster
1.000	PEG-40 Hydrogenated	Viscosity
	Castor Oil.sup.7)	adjuster .sup.1) EDETA B POWDER; trademark and origin: BASF .sup.2) Texapon
	NSO IS; trademark and origin: COGNIS .sup.3)MERQUAT 550; trademark and origin: LUBRIZOL .sup.4)DEHYTON AB-30; trademark and origin: COGNIS .sup.5)GLUCAMATE LT; trademark and origin: LUBRIZOL .sup.6)EUPERLAN PK 3000 AM; trademark and origin: COGNIS .sup.7)CREMOPHOR RH 40; trademark and origin: BASF	

[0485] Ingredients are mixed, pH is adjusted to 4.5 (Viscosity: 4000cPo+/-1500cPo (Brookfield RV/Spindle #4/20 RPM))

Example 31

Hand Dishwash

[0486] A sufficient amount of exemplified microcapsules is weighed and mixed in the following composition to add the equivalent of 0.2% perfume.

TABLE-US-00033 TABLE 33 Hand dishwash composition

Amount	Ingredients (% wt)	Function
20	Linear alkylbenzene sulfonic acid .sup.(1)	Anionic surfactant
3.5	Diethanolamide .sup.(2)	Foam booster
3.4	Sodium Hydroxide (50%) .sup.(3)	pH Adjuster/neutralizer
2.5	Secondary alcohol ethoxolate .sup.(4)	Non-ionic surfactant
6.3	Sodium xylene sulfonate	Hydrotrope
64.3	Water	Solvent

.sup.(1) Biosoft S-118 ®; trademark and origin: Stepan Company .sup.(2) Ninol 40-CO ®; trademark and origin: Stepan Company .sup.(3) Stepanate SXS ®; trademark and origin: Stepan Company .sup.(4) Tergitol 15-S-9 ®; trademark and origin: Dow Chemical Company

[0487] Water with sodium hydroxide and diethanolamide are mixed. LAS is added. After the LAS is neutralized, the remaining ingredients are added. The pH was Checked (=7-8) and adjusted if necessary.

Example 32

Toothpaste Formulation

[0488] A sufficient amount of a microcapsule slurry M (prepared according to the protocol disclosed in example 1 except that a menthol flavor is encapsulated) is weighed and mixed in the following composition to add the equivalent of 0.2% flavor.

TABLE-US-00034 TABLE 34 Toothpaste formulation

Ingredients	Amount (% wt)
Polyethylene glycol 400	2.0%
Xanthan Gum	0.6%
Sorbitol 70% Solution	50%
Sodium Fluoride	0.220%
Sodium Benzoate	0.2%
Water	15.230%
Hydrated Silica.sup.1)	22.0%
Hydrated Silica.sup.2)	7.0%
Titanium Dioxide CI77891	0.5%
Sodium Lauryl Sulfate	1.250%
Flavor	1.2%
TOTAL	100%

.sup.1)Tixosil 73; trademark and origin: .sup.2)Tixosil 43; trademark and origin:

Example 33

Dicalcium Phosphate Based Toothpaste Formulation

[0489] A sufficient amount of a microcapsule slurry M (prepared according to the protocol disclosed in example 1 except that a menthol flavor is encapsulated) is weighed and mixed in the following composition to add the equivalent of 0.2% flavor.

TABLE-US-00035 TABLE 35 Toothpaste formulation

Ingredients	Amount (% wt)
Sodium carboxymethyl cellulose	1.2%
Flavor	1.2%
DI/Purified Water	Q.S to Final Wt.
Sodium Lauryl Sulfate	1.3%
Glycerine	20.0%
Sodium Saccharin	0.2%
Dicalcium phosphate dihydrate	36.0%
Methylparaben	0.2%
Silica.sup.1)	3.0%
TOTAL	100%

.sup.1)Aerosil ®200; trademark and origin:

Example 34

Mouthwash Alcohol Free Formulation

[0490] A sufficient amount of a microcapsule slurry M (prepared according to the protocol disclosed in example 1 except that a menthol flavor is encapsulated) is weighed and mixed in the following composition to add the equivalent of 0.2% flavor.

TABLE-US-00036 TABLE 36 Mouthwash formulation

Ingredients	Amount (% wt)
Propylene Glycol	10%
Flavor	0.240%
DI/Purified Water	Q.S to Final Wt.
Poloxamer 407 NF	0.240%
Sodium Lauryl Sulfate	0.040%
Sorbitol 70% Solution	10.0%
Sodium Saccharin	0.030%
Glycerine	3.0%
Sodium Benzoate	0.100%
Sucralose	0.020%
Benzoic Acid	0.050%
TOTAL	100%

Example 35

Mouthwash Formulation

[0491] A sufficient amount of a microcapsule slurry M (prepared according to the protocol disclosed in example 1 except that a menthol flavor is encapsulated) is weighed and mixed in the following composition to add the equivalent of 0.2% flavor.

TABLE-US-00037 TABLE 37 Mouthwash formulation

Ingredients	Amount (% wt)
Ethyl Alcohol 190 Proof	15.0%
Flavor	0.240%
DI/Purified Water	Q.S to Final Wt.
Poloxamer 407 NF	0.240%
Sodium Lauryl Sulfate	0.040%
Sorbitol 70% Solution	10.0%
Sodium Saccharin	0.030%
Glycerine	3.0%
Sodium Benzoate	0.100%
Sucralose	0.020%
Benzoic Acid	0.050%
TOTAL	100%

Claims

1. A core-shell microcapsule comprising: a core comprising a hydrophobic material, and a polymeric shell comprising a protein selected from the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof.

2. The core-shell microcapsule according to claim 1, wherein the polymeric shell comprises a material selected from the group consisting of polyamide, polyurea, polyurethane, polyester, polyacrylate, polysiloxane, polycarbonate, polysulfonamide, polymers of urea and formaldehyde, melamine and formaldehyde, melamine and urea, or melamine and glyoxal and mixtures thereof.

3. The core-shell microcapsule according to claim 1, wherein the polymeric shell is a polyamide-

based shell.

4. The core-shell microcapsule according to claim 3, wherein the polyamide-based shell is obtained from the reaction between an acyl chloride and at least one amino compound.
5. The core-shell microcapsule according to claim 3, wherein the polyamide-based shell is obtained from the reaction between an acyl chloride and at least two amino compounds.
6. The core-shell microcapsule according to claim 4, wherein the amino compound is selected from the group consisting of cystamine, cystamine hydrochloride, cystine, cystine hydrochloride, cystine dialkyl ester, cystine dialkyl ester hydrochloride, a xylylene diamine, 1,2-diaminocyclohexane, 1,4-diaminocyclohexane, polyetheramines, ethylene diamine, diethylene triamine, spermine, spermidine, polyamidoamine (PAMAM), guanidine carbonate, chitosan, tris-(2-aminoethyl)amine, 3-aminopropyltriethoxysilane, 1,4 Diaminobutane, 2,2Dimethyl-1,3-propanediamine, 1,3-diaminopentane, 1,2 Diaminopropane, triethylenetetramine, 1,3-diaminopropane; urea; ethylene urea; aminoguanidine bicarbonate; 1-(2-aminoethyl) imidazolidin-2-one; N-(3-aminopropyl)-N-dodecylpropane-1,3-diamine; N1-(2-Aminoethyl)-N1-dodecyl-1,2-ethanediamine; aminoethylethanolamine; N1-(3-aminopropyl) propane-1,3-diamine, polyethyleneimine, amino-compound such as L-Lysine, L-Arginine, L-Histidine, L-Tryptophane, L-Serin, L-Glutamine, L-Threonine, L-Leucine, and/or its derived oligomers and polymers, and mixtures thereof.
7. The core-shell microcapsule according to claim 1, wherein the protein is selected from the group consisting of potato protein, chickpea protein, pea protein and mixtures thereof.
8. The core-shell microcapsule according to claim 4, wherein the acyl chloride is a compound of formula (I) ---X---C(=O)--- wherein n is an integer varying between 1 and 8, and wherein X is an (n+1)-valent C₂ to C₄₅ hydrocarbon group optionally comprising at least one group selected from the group consisting of (i) to (xi), ---R--- wherein R is a hydrogen atom or an alkyl group.
9. The microcapsule core-shell according to claim 4, wherein the polyamide-based shell is obtained from the reaction between an acyl chloride and at least one amino compound and wherein the at least one amino compound is L-Lysine.
10. A process for preparing a core-shell microcapsule slurry comprising the steps of: a) preparing an oil phase comprising a hydrophobic material, preferably a perfume to form an oil phase; b) dispersing the oil phase obtained in step a) into a water phase to form an oil-in water emulsion; and c) performing a curing step to form microcapsules in the form of a slurry; wherein a polyfunctional monomer is added in the oil phase and/or in the water phase, and wherein a protein selected from the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase.
11. The process according to claim 10, wherein the polyfunctional monomer is selected from the group consisting of at least one acyl chloride, a polyisocyanate, poly anhydride, polyepoxide, acrylate monomers, polyalkoxysilane, and mixtures thereof.
12. The process according to claim 10, wherein it comprises the steps of: a) preparing an oil phase comprising an acyl chloride and a hydrophobic material, to form an oil phase; b) dispersing the oil phase obtained in step a) into a water phase to form an oil-in water emulsion; and c) performing a curing step to form microcapsules in the form of a slurry; wherein at least one amino-compound is added in the water phase before the formation of the oil-in-water emulsion and/or in the oil-in water emulsion obtained after step b), and wherein a protein selected from the group consisting of potato protein, chickpea protein, pea protein, algae protein, faba bean protein, barley protein, oat protein, wheat gluten protein, lupin protein, and mixtures thereof is added in the oil phase and/or in the water phase.
13. A perfuming composition comprising (i) the core-shell microcapsule according to claim 1, wherein the hydrophobic active ingredient comprises a perfume, (ii) at least one ingredient selected from the group consisting of a perfumery carrier and a perfumery base, and (iii) optionally at least

one perfumery adjuvant.

14. A consumer product comprising: a personal care active base, and the core-shell microcapsule according to claim 1, wherein the consumer product is in the form of a personal care composition.

15. A consumer product comprising: a home care or a fabric care active base, and the core-shell microcapsule according to claim 1, wherein the consumer product is in the form of a home care or a fabric care composition.

16. A consumer product comprising: a personal care active base, and the perfuming composition according to claim **13**, wherein the consumer product is in the form of a personal care composition.

17. A consumer product comprising: a home care or a fabric care active base, and the perfuming composition according to claim **13**, wherein the consumer product is in the form of a home care or a fabric care composition.

18. The core-shell microcapsule according to claim 1, wherein the core comprises a perfume oil.

19. The core-shell microcapsule according to claim 8, wherein n is an integer varying between 1 and 6.

20. The core-shell microcapsule according to claim 8, wherein R is a methyl or an ethyl group or a hydrogen atom.
