

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12397496
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Susnjara; Kenneth J. et al.

Methods and apparatus for compressing material during additive manufacturing

Abstract

An additive manufacturing device and method for delivering a flowable material from a nozzle of a programmable computer numeric control (CNC) machine, and compressing the flowable material with a compression roller. In one embodiment, the device includes a nozzle configured to deposit a flowable material on a surface; and a roller configured to compress the deposited flowable material, wherein the roller comprises: a flat center portion having a constant diameter; and opposed end portions, wherein each end portion extends outwardly from the flat center portion, and wherein a radially outermost surface of each end portion is angled relative a rotational axis of the roller.

Inventors:	Susnjara; Kenneth J. (Birdseye, IN), Vaal; Scott G. (Jasper, IN)
Applicant:	Thermwood Corporation (Dale, IN)
Family ID:	1000008781149
Assignee:	Thermwood Corporation (Dale, IN)
Appl. No.:	18/913440
Filed:	October 11, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20250033268 A1	Jan. 30, 2025

Related U.S. Application Data

continuation parent-doc US 18419036 20240122 US 12138849 child-doc US 18913440
continuation parent-doc US 17365352 20210701 US 11911953 20240207 child-doc US 18419036
continuation parent-doc US 16935981 20200722 US 11065808 20210720 child-doc US 17365352

Publication Classification

Int. Cl.: **B29C67/00** (20170101); **B29C64/106** (20170101); **B29C64/194** (20170101);
B29C64/218 (20170101); B33Y10/00 (20150101); B33Y30/00 (20150101)

U.S. Cl.:

CPC **B29C64/106** (20170801); **B29C64/194** (20170801); **B29C64/218** (20170801);
B33Y10/00 (20141201); B33Y30/00 (20141201)

Field of Classification Search

CPC: B33Y (10/00); B33Y (30/00); B29C (64/218); B29C (64/106); B29C (64/194)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5063014	12/1990	Cakmakci	N/A	N/A
6082292	12/1999	Denes	118/729	B29C 59/14
7731816	12/2009	Oldani et al.	N/A	N/A
7810539	12/2009	Mischler et al.	N/A	N/A
8151854	12/2011	Oldani	N/A	N/A
8534338	12/2012	Oldani et al.	N/A	N/A
8954180	12/2014	Oldani	N/A	N/A
2002/0062909	12/2001	Jang	156/307.3	B33Y 10/00
2002/0079601	12/2001	Russell et al.	N/A	N/A
2002/0121712	12/2001	Schroeder	N/A	N/A
2003/0151167	12/2002	Kritchman et al.	N/A	N/A
2005/0218552	12/2004	Van Erden et al.	N/A	N/A
2006/0202384	12/2005	Duong et al.	N/A	N/A
2006/0249256	12/2005	Borgmann	156/425	B29C 70/32
2007/0044899	12/2006	Tingley	N/A	N/A
2008/0006017	12/2007	Rindels	N/A	N/A
2008/0303182	12/2007	Breyer	N/A	N/A
2009/0014116	12/2008	Takada et al.	N/A	N/A
2009/0117837	12/2008	Choi	N/A	N/A
2010/0109185	12/2009	Ogawa et al.	N/A	N/A
2010/0200168	12/2009	Oldani et al.	N/A	N/A
2013/0081751	12/2012	Kokaji et al.	N/A	N/A
2013/0126095	12/2012	Johns et al.	N/A	N/A
2016/0243765	12/2015	Sasaki et al.	N/A	N/A
2017/0021565	12/2016	Deaville	N/A	N/A
2018/0050502	12/2017	Oldani	N/A	N/A
2019/0232566	12/2018	Bosveld	N/A	N/A

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This patent application is a continuation of and claims the benefit of priority to U.S. application Ser. No. 18/419,036, filed on Jan. 22, 2024, which is a continuation of U.S. application Ser. No. 17/365,352, filed on Jul. 1, 2021, now U.S. Pat. No. 11,911,953, issued on Feb. 27, 2024, which is a continuation of U.S. application Ser. No. 16/935,981, filed on Jul. 22, 2020, now U.S. Pat. No. 11,065,808, issued on Jul. 20, 2021, which is a continuation of U.S. application Ser. No. 16/572,897, filed on Sep. 17, 2019, now U.S. Pat. No. 10,744,709, issued on Aug. 18, 2020, which is a divisional of U.S. application Ser. No. 15/435,408, filed on Feb. 17, 2017, now U.S. Pat. No. 10,449,710, issued on Oct. 22, 2019, the entireties of which are incorporated herein by reference.

TECHNICAL FIELD

(1) Aspects of the present disclosure relate to apparatus and methods for fabricating components. In some instances, aspects of the present disclosure relate to apparatus and methods for fabricating components (such as, e.g., automobile parts, medical devices, machine components, consumer products, etc.) via additive manufacturing techniques or processes, such as, e.g., 3D printing manufacturing techniques or processes.

BACKGROUND

(2) Additive manufacturing techniques and processes generally involve the buildup of one or more materials to make a net or near net shape (NNS) object, in contrast to subtractive manufacturing methods. Though “additive manufacturing” is an industry standard term (ASTM F2792), additive manufacturing encompasses various manufacturing and prototyping techniques known under a variety of names, including freeform fabrication, 3D printing, rapid prototyping/tooling, etc. Additive manufacturing techniques are capable of fabricating complex components from a wide variety of materials. Generally, a freestanding object can be fabricated from a computer-aided design (CAD) model.

(3) One such process, commonly referred to as Fused Deposition Modeling (FDM), comprises a process of melting a very thin layer of a flowable material (e.g., a thermoplastic material), and applying this material in layers to produce a final part. This is commonly accomplished by passing a continuous thin filament of thermoplastic material through a heated nozzle, which melts the thermoplastic material and applies it to the structure being printed. The heated material then is applied to the existing structure in thin layers, melting and fusing with the existing material to produce a solid finished product.

(4) A common method of additive manufacturing, or 3D printing, generally includes forming and extruding a bead of flowable material (e.g., molten thermoplastic), applying the bead of material in a strata of layers to form a facsimile of an article, and machining such facsimile to produce an end product. Such a process is generally achieved by means of an extruder mounted on a computer numeric controlled (CNC) machine with controlled motion along at least the X, Y, and Z-axes. In some cases, the flowable material, such as, e.g., molten thermoplastic material, may be infused with a reinforcing material (e.g., strands of fiber) to enhance the material's strength.

(5) The flowable material, while generally hot and pliable, may be deposited upon a substrate (e.g., a mold), pressed down or otherwise flattened to some extent, and leveled to a consistent thickness, preferably by means of a tangentially compensated roller mechanism. The flattening process may aid in fusing a new layer of the flowable material to the previously deposited layer of the flowable

material. In some instances, an oscillating plate may be used to flatten the bead of flowable material to a desired thickness, thus effecting fusion to the previously deposited layer of flowable material. The deposition process may be repeated so that each successive layer of flowable material is deposited upon an existing layer to build up and manufacture a desired component structure. When executed properly, the new layer of flowable material may be deposited at a temperature sufficient enough to allow a new layer of such material to melt and fuse with a previously deposited layer, thus producing a solid part.

(6) The process of 3D-printing a part, which utilizes a large print bead to achieve an accurate final size and shape, requires a two-step process. This two-step process, commonly referred to as near-net-shape, begins by printing a part to a size slightly larger than needed, then machining, milling or routing the part to the final size and shape. The additional time required to trim the part to final size is more than compensated for by the much faster printing process.

(7) In the practice of the aforementioned process, a major deficiency has been noted. In creating parts with successive layers, the layers must be applied in uniform, smooth beads with no trapped air between layers. In applying a successive layer of material upon an existing layer, the existing layer must be leveled smoothly in order to effectively bond with the successive layer. The successive layer of material has to be leveled smoothly and trapped air must be pressed out between the layers. The layers must be of uniform width, height, and shape, in order to produce consistent parts. Also, the flattening device must be able to navigate corners without gouging in, or dragging the flowable material. Smooth layers allow for better bonding between layers, resulting in better strength characteristics in the finished part. Uniform layers allow for consistent bonding of layers, plus less machining time in order to get a smooth part. Air in or between layers can cause voids in the part when machined, which can weaken the bond, and render the part unusable.

(8) In past attempts to address the aforementioned concerns, a number of different methods have been attempted. One such attempted method involves the use of an oscillating plate for tamping the bead to achieve both leveling and bonding. Such a device, however, does not create a smooth bead of uniform width, and therefore requires extra machining, among other problems. While the use of a roller is the preferred method for achieving a smooth and well-bonded strata of layers, attempts by the prior art to employ such a method have resulted in unsatisfactory results.

(9) Another method that has been employed is the use of a grooved roller. A grooved roller, however, does not create a smooth bead, nor does it remove the trapped air between the layers. Attempts to employ a smooth, straight roller have been met with some success; however this method has likewise given rise to unsatisfactory results. The desired compression roller must be somewhat wider than the final compressed surface of the deposited layer that it is flattening. This is due to a number of factors intrinsic to the process, including coverage requirements when negotiating curves and corners in the deposition process.

(10) Another inherent characteristic of the additive manufacturing process is the slight decompression of the deposited layer, which occurs immediately after the compression roller passes over the bead of molten material. Such action results in the surface of the final flattened layer rising up, and remaining slightly higher than the bottom of the compression roller. When an applicator head rotates to execute a change in tool-path direction, the edges, as well as the outer regions of the roller tend to engage the surface of the final flattened layer, since it is slightly higher than the bottom of the roller, resulting in the roller gouging and dragging the deposited material during the transition. A similar problem occurs when depositing a layer adjacent to a previously deposited layer. In such a case, the existing layer is again, slightly higher than the bottom of the roller, the result of which is the same type of problem encountered during directional transition. It is therefore desirable to provide a compression roller of a design that will eliminate, or greatly mitigate the negative aspects of a typical, straight cylindrical roller.

SUMMARY

(11) Aspects of the present disclosure relate to, among other things, methods and apparatus for

fabricating components via additive manufacturing, such as, e.g., 3D printing techniques. Each of the aspects disclosed herein may include one or more of the features described in connection with any of the other disclosed aspects. In one aspect, the disclosure describes, among other things, a compression roller that can flatten and level layers of molten material in the additive manufacturing process, without gouging into, or dragging the previously-deposited material.

(12) The description below provides a compression roller with a flat center portion for engaging and flattening the deposited bead, with the outer extremities of said roller gradually tapering to the ends in a slight elliptical curve. The flat surface of such a roller provides smooth compression and bonding of the deposited material layer, while the gradually-curved outer surface facilitates destruction-free tracking along curved portions of the deposited layer, as well as during directional changes in the tool path.

(13) In one example, the additive manufacturing device comprises a nozzle configured to deposit a flowable material on a surface; and a roller configured to compress the deposited flowable material, wherein the roller comprises: a flat center portion having a constant diameter; and opposed end portions, wherein each end portion extends outwardly from the flat center portion, and wherein a radially outermost surface of each end portion is angled relative a rotational axis of the roller.

(14) In another example, the additive manufacturing device comprises a nozzle configured to deposit a flowable material; and a roller configured to compress the deposited flowable material, wherein the roller comprises: a cylindrical center portion having a first diameter; and opposed first and second end portions having second and third diameters respectively, wherein the first and second end portions extend from the center portion, and wherein the first diameter is greater than the second and third diameters.

(15) In another aspect, the present disclosure is directed to an additive manufacturing method for compressing a flowable material with a compression roller. In one embodiment, the method comprising depositing a layer of a flowable material on to a surface; and compressing the layer of the flowable material with a roller, wherein the roller comprises: a flat center portion having a constant diameter; and opposed end portions, wherein each end portion extends outwardly from the center portion, and wherein a radially outermost surface of each end portion is angled relative a rotational axis of the roller.

(16) As used herein, the terms “comprises,” “comprising,” or any other variation thereof, are intended to cover a non-exclusive inclusion, such as a process, method, article, or apparatus. The term “exemplary” is used in the sense of “example,” rather than “ideal.”

(17) It may be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the disclosure, as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate exemplary aspects of the present disclosure and together with the description, serve to explain the principles of the disclosure.

(2) FIG. 1 is a perspective view of an exemplary CNC machine operable pursuant to an additive manufacturing process to form articles, according to an aspect of the present disclosure;

(3) FIG. 2 is an enlarged perspective view of an exemplary carrier and applicator assembly of the exemplary CNC machine shown in FIG. 1;

(4) FIG. 3 is an enlarged cross-sectional view of an exemplary applicator head assembly shown in FIG. 2;

(5) FIG. 4 is an enlarged cross-sectional view of an exemplary deposition head and compression roller assembly, illustrating the slight decompression of a deposited layer, which occurs

immediately after the compression roller passes over the deposited bead of molten material;

(6) FIG. 5a is an enlarged plan view of an exemplary carrier and applicator assembly of the exemplary CNC additive manufacturing machine shown in FIG. 1;

(7) FIG. 5b is an enlarged plan view of an exemplary bead compression roller, illustrating the different surface features of the roller;

(8) FIG. 6a is an enlarged cross-sectional view of an exemplary compression roller, with an elliptically tapered outer surface feature, compressing a molten material bead alongside a previously-deposited and compressed layer of material; and

(9) FIG. 6b is an enlarged cross-sectional perspective view of an exemplary material compression roller, with an elliptically tapered outer surface feature, executing a tool-path directional change.

DETAIL DESCRIPTION OF THE INVENTION

(10) The present disclosure is drawn to, among other things, methods and apparatus for fabricating multiple components via additive manufacturing techniques, such as, e.g., 3D printing. More particularly, the methods and apparatus described herein comprise a method and apparatus for eliminating, or otherwise substantially reducing damage to the surface of deposited and compressed molten material bead(s) during the stratification process of additive manufacturing by, e.g., providing a compression roller that can flatten and level layers of molten material in the additive manufacturing process, without gouging into, or dragging the previously-deposited material.

(11) For purposes of brevity, the methods and apparatus described herein will be discussed in connection with fabricating parts from thermoplastic materials. However, those of ordinary skill in the art will readily recognize that the disclosed apparatus and methods may be used with any flowable material suitable for additive manufacturing, such as, e.g., 3D printing.

(12) In one aspect, the present disclosure is directed to an extruder-based 3D printing head including a compression roller having a shape that facilitates compressing a bead of flowable material (e.g., a thermoplastic material) by eliminating distortion of the layered and compressed surface. With reference now to FIG. 1 of the drawings, there is illustrated a programmable computer numeric control (CNC) machine 1 embodying aspects of the present disclosure. A controller (not shown) may be operatively connected to machine 1 for displacing an application nozzle along a longitudinal line of travel or x-axis, a transverse line of travel or a y-axis, and a vertical line of travel or z-axis, in accordance with a program inputted or loaded into the controller for performing an additive manufacturing process to replicate a desired component. CNC machine 1 may be configured to print or otherwise build 3D parts from digital representations of the 3D parts (e.g., AMF and STL format files) programmed into the controller. For example, in an extrusion-based additive manufacturing system, a 3D part may be printed from a digital representation of the 3D part in a layer-by-layer manner by extruding a flowable material. The flowable material may be extruded through an extrusion tip carried by a print head of the system, and is deposited as a sequence of beads or layers on a substrate in an x-y plane. The extruded flowable material may fuse to previously deposited material, and may solidify upon a drop in temperature. The position of the print head relative to the substrate is then incrementally advanced along a z-axis (perpendicular to the x-y plane), and the process is then repeated to form a 3D part resembling the digital representation.

(13) Machine 1 includes a bed 20 provided with a pair of transversely spaced side walls 21 and 22, a gantry 23 supported on side walls 21 and 22, carriage 24 mounted on gantry 23, a carrier 25 mounted on carriage 24, an extruder 61, and an applicator assembly 43 mounted on carrier 25. Supported on bed 20 between side walls 21 and 22 is a worktable 27 provided with a support surface disposed in an x-y plane, which may be fixed or displaceable along an x-axis. In the displaceable version, the worktable may be displaceable along a set of rails mounted on the bed 20 by means of servomotors and rails 28 and 29 mounted on the bed 20 and operatively connected to the worktable 27. Gantry 23 is disposed along a y-axis, supported at the ends thereof on end walls 21 and 22, either fixedly or displaceably along an x-axis on a set of guide rails 28 and 29 provided

on the upper ends of side walls **21** and **22**. In the displaceable version, the gantry **23** may be displaceable by a set of servomotors mounted on the gantry **23** and operatively connected to tracks provided on the side walls **21** and **22** of the bed **20**. Carriage **24** is supported on gantry **23** and is provided with a support member **30** mounted on and displaceable along one or more guide rails **31**, **32** and **33** provided on the gantry **23**. Carriage **24** may be displaceable along a y-axis on one or more guide rails **31**, **32** and **33** by a servomotor mounted on the gantry **23** and operatively connected to support member **30**. Carrier **25** is mounted on a set of spaced, vertically disposed guide rails **34** and **35** supported on the carriage **24** for displacement of the carrier **25** relative to the carriage **24** along a z-axis. Carrier **25** may be displaceable along the z-axis by a servomotor mounted on the carriage **24** and operatively connected to the carrier **25**.

(14) As best shown in FIG. 2, fixedly mount to carrier **25** is a positive displacement gear pump **74**, driven by a servomotor **75**, through a gearbox **76**. Gear pump **74** receives molten plastic from extruder **61** shown in FIG. 1. As shown in FIG. 2, a tangentially compensated bead-shaping compression roller **59**, rotatably mounted in carrier bracket **47**, provides a means for flattening and leveling a bead of flowable material (e.g., a thermoplastic material), as also shown in FIG. 3. Carrier bracket **47** may be adapted to be rotationally displaced by means of a servomotor **60**, as shown in FIG. 2), through a sprocket **56** and drive-chain **65** arrangement.

(15) With continuing reference to FIG. 3, applicator head **43** may include a housing **46** with a roller bearing **49** mounted therein. Carrier bracket **47** is fixedly mounted to an adaptor sleeve **50**, journaled in bearing **49**. As best shown in FIGS. 2-3, a bead of a flowable material (e.g., a thermoplastic material) under pressure from a source (e.g., one or more extruder **61** and an associated polymer or gear pump) disposed on carrier **25**, to applicator head **43**, may be fixedly (or removably) connected to, and in communication with nozzle **51**. In use, the flowable material **53** (e.g., melted thermoplastic) may be heated sufficiently to form a molten bead thereof, delivered through applicator nozzle **51**, to form uniform, smooth multiple rows of deposited material free of trapped air on to surface **27**. Such beads of molten material may be flattened, leveled, and/or fused to adjoining layers by bead-shaping compression roller **59**, to form an article. Even though compression roller **59** is depicted as being integral with application head **43**, compression roller **59** may be separate and discrete from applicator head **43**.

(16) In some embodiments, the deposited material **53** may be provided with a suitable reinforcing material, such as, e.g., fibers that facilitate and enhance the fusion of adjacent layers of extruded flowable material **53**.

(17) In some embodiments, machine **1** may include a velocimetry assembly (or multiple velocimetry assemblies) configured to determine flow rates (e.g., velocities and/or volumetric flow rates) of material **53** being delivered from applicator head **43**. The velocimetry assembly preferably transmits signals relating to the determined flow rates to the aforementioned controller coupled to machine **1**, which may then utilize the received information to compensate for variations in the material flow rates.

(18) In the course of fabricating a component, pursuant to the methods described herein, the control system of the machine **1**, in executing the inputted program, may control several servomotors described above to displace the gantry **23** along the x-axis, displace the carriage **24** along the y-axis, displace the carrier **25** along a z-axis, and rotates bracket **47** about a z-axis while compression roller **59** forms uniform, smooth rows of deposited material **52** free of trapped air to create an article.

(19) With reference now to FIG. 4, there is illustrated a cross-sectional schematic representation of a flowable material (e.g., melted thermoplastic) extrusion and application system. During an additive manufacturing process, there is a slight decompression of the deposited layer **53**, which occurs immediately after the compression roller **59** passes over the bead of flowable material (e.g., melted thermoplastic material). Such a decompression results in the surface of the final flattened layer rising up, and remaining slightly higher than the bottom of the compression roller **59**. This

decompression is best shown FIG. 4, where distance A illustrates a difference in height between the bottom apex of the compression roller 59, and the top of the decompressed material bead 53.

Owing to this decompression, when the applicator head 43 rotates to execute a change in tool-path direction, the edges, as well as the outer regions, of the roller 59 tend to engage the surface of the final flattened layer, since it is slightly higher than the bottom apex of the roller, resulting in the roller gouging and/or dragging the deposited material during the transition.

(20) With reference now to FIGS. 5a and 5b, the surface-contour of compression roller 59 can be seen in both enlarged plan views. Compression roller 59 comprises a flat center portion C for engaging and flattening the deposited bead, with the outer extremities of said roller gradually tapering to the ends in a slight elliptical curve, as shown as portions A and B in FIG. 5b. The flat surface C of roller 59 provides smooth compression and bonding of the deposited material layer, while the gradually-curved outer surfaces facilitates destruction-free tracking along curved portions of the deposited layer, as well as during directional changes in the tool path.

(21) In FIG. 5b, the surface features are annotated as A, B, and C for descriptive purpose. A and B show the elliptically-tapered outer segments of the roller, while C shows the flat middle feature of the roller. The gradual outer taper of roller 59 prevents the roller 59 from gouging and dragging molten thermoplastic material from the surface of the flattened layer when the roller is advanced in a non-linear direction (e.g., when the roller turns a corner) during the stratification process, as well as when depositing and compressing a bead of flowable material (e.g., melted thermoplastic) adjacent to a previously-deposited adjoining layer, which may still be molten. By comparison, a completely cylindrical compression roller (e.g., a roller without the tapered segments A and B depicted in FIG. 5b) would gouge and drag the material while navigating around corners and curves, as the entire roller surface would be engaged with the slightly-decompressed and raised material surface. Compression roller 59 smooths and bonds the layer with the flat portion of the roller, and the gradual tapering of the outer surfaces allows it to negotiate around the corners without producing objectionable surface imperfections.

(22) FIG. 6a, which depicts a cut-away end view of deposited strata, exemplifies the bead compression process, using the described compression roller 59 during the deposition of a bead of flowable material (e.g., melted thermoplastic) adjacent to a previously deposited and compressed bead. Tapered end 63 of the compression roller 59 does not substantially engage a previously deposited layer 72, and therefore has minimal or no effect on the surface of layer 72. In some embodiments, the tapered end 63 of the compression roller 59 may be tapered at both ends, as shown in FIG. 6a. In other embodiments, compression roller 59 may include only a single tapered end 63. In some embodiments, the tapered end 63 may be angled “a” approximately 1 to 15 degrees relative to the surface of the center, flat portion of roller 59. In some other embodiments, tapered end 63 may include a non-linear relief (e.g., the relief is not a straight line, but a taper curving away from the radially outermost surface of compression roller 59).

(23) With reference now to FIG. 6b, which is a cut-away view of strata deposited in two directions, there is shown, an exemplary view of the compression roller 59, executing a change of direction in the bead deposition process. The tapered portion 63 of roller 59 does not engage the material on the adjoining side of the article, because roller 59 is slightly tapered to prevent any substantial contact with the surface of that side of the deposited strata of previously deposited layers. After deposition of a flowable material (e.g., melted thermoplastic) on surface 27, as shown in FIG. 3, and while the topmost layer of deposited strata 72, as shown in FIG. 6a, is cooling (e.g., the melted material has not completely solidified), compression roller 59 is used to flatten deposited strata 72 to create a uniform deposited layer. In some examples, however, compression roller 72 must be used to flatten deposited strata 72 in a non-linear manner (e.g., when navigating a corner or curve). In such instances, compression roller 59 is used to compress the unsolidified top-most layer of deposited strata 72, while navigating around the corner or curve, such that any flowable material of the top most layer of deposited strata 72 is not gouged and/or dragged. Moreover, when roller 59 navigates

a corner or curve, the roller 59 would be engaged with the slightly-decompressed and raised material surface, as previously described above.

(24) While principles of the present disclosure are described herein with reference to illustrative embodiments for particular applications, it should be understood that the disclosure is not limited thereto. Those having ordinary skill in the art and access to the teachings provided herein will recognize additional modifications, applications, embodiments, and substitution of equivalents all fall within the scope of the embodiments described herein. Accordingly, the inventions described herein are not to be considered as limited by the foregoing description.

Claims

1. An additive manufacturing device comprising: a carrier movable along an x-axis, a y-axis, and a z-axis; a roller connected to the carrier and configured to compress material during additive manufacturing, wherein the roller comprises: a center portion with a width, the center portion having a constant diameter across the entire width; and opposed end portions each abutting the center portion, each end portion extending outwardly from the center portion and having a non-linear surface curving away from a radially outermost surface of the center portion; and a control system configurable to: control movement of the carrier along the x-axis, y-axis, and z-axis; and rotate the roller about the z-axis.
2. The additive manufacturing device of claim 1, wherein the non-linear surface of each end portion includes a curve that tapers away from the radially outermost surface of the center portion.
3. The additive manufacturing device of claim 1, wherein the roller is further configured to rotate about an axis perpendicular to the z-axis.
4. The additive manufacturing device of claim 1, wherein the control system is configurable to synchronize rotation of the roller with movement of the carrier along a deposition path.
5. The additive manufacturing device of claim 1, further comprising a first servomotor configured to move the carrier along the x-axis, a y-axis, and a z-axis.
6. The additive manufacturing device of claim 1, wherein the control system is configurable to adjust the rotation of the roller about the z-axis in response to changes in a deposition path direction.
7. The additive manufacturing device of claim 1, wherein each opposed end portion of the roller has a diameter that decreases from the center portion toward an axial end of the roller.
8. The additive manufacturing device of claim 1, wherein the roller is connected to the carrier via a bracket, and a servomotor is connected to the roller via a sprocket and chain assembly.
9. The additive manufacturing device of claim 1, wherein the roller is configured to compress a flowable material during additive manufacturing.
10. A roller assembly for an additive manufacturing device, the roller assembly comprising: a roller comprising: a center portion with a width, the center portion having a constant diameter across the entire width; and opposed end portions each abutting the center portion, each end portion extending outwardly from the center portion and having a relief curving away from a radially outermost surface of the center portion; and a servomotor operatively connected to the roller and configurable to rotationally displace the roller about an axis.
11. The roller assembly of claim 10, wherein the relief of each end portion comprises a non-linear taper.
12. The roller assembly of claim 10, wherein the servomotor is connected to the roller via a sprocket mechanism.
13. The roller assembly of claim 10, further comprising a bracket supporting the roller, wherein the bracket is rotationally displaceable about the axis by the servomotor.
14. The roller assembly of claim 10, wherein the axis about which the roller is rotatable is perpendicular to a direction of material deposition of the additive manufacturing device.

15. The roller assembly of claim 10, wherein the center portion and the end portions are formed integrally.

16. The roller assembly of claim 10, wherein the roller is configured to compress a flowable material during additive manufacturing.

17. The roller assembly of claim 10, wherein the relief, by curving away from the radially outermost surface, is configured to reduce material distortion during deposition along curved paths.

18. The roller assembly of claim 10, wherein the servomotor is connected to the roller via a sprocket and chain drive mechanism, and wherein the sprocket and chain drive mechanism comprises a first sprocket connected to the servomotor, a second sprocket connected to the roller, and a chain connecting the sprockets.

19. A system for forming a part using additive manufacturing, the system comprising: a worktable having a horizontally-extending surface; an applicator assembly movable relative to the worktable; a first servomotor configured to move the applicator assembly; a roller connected to the applicator assembly and configured to compress material during additive manufacturing, wherein the roller comprises: a center portion with a constant diameter; a first end portion abutting a first end of the center portion and having a first non-linear surface curving away from first end of the center portion; a second end portion abutting a second end of the center portion opposite the first end and having a second non-linear surface curving away from second end of the center portion; and a control system configurable to: control actuation of the first servomotor to move the applicator assembly; and control a position of the roller relative to the applicator assembly during additive manufacturing.

20. The system of claim 19, further comprising a second servomotor operatively connected to the roller and configurable to rotationally displace the roller about an axis that intersects the horizontally-extending surface.
