

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12400936

Kind Code

B2

Date of Patent

August 26, 2025

Inventor(s)

Chuang; Lipu Kris et al.

Stacked memory cube with integrated thermal path for enhanced heat dissipation

Abstract

A memory device including a base chip and a memory cube mounted on and connected with the base chip is described. The memory cube includes multiple stacked tiers, and each tier of the multiple stacked tiers includes semiconductor chips laterally wrapped by an encapsulant and a redistribution structure. The semiconductor chips of the multiple stacked tiers are electrically connected with the base chip through the redistribution structures in the multiple stacked tiers. The memory cube includes a thermal path structure extending through the multiple stacked tiers and connected to the base chip. The thermal path structure has a thermal conductivity larger than that of the encapsulant. The thermal path structure is electrically isolated from the semiconductor chips in the multiple stacked tiers and the base chip.

Inventors: Chuang; Lipu Kris (Hsinchu, TW), Liu; Chung-Shi (Hsinchu, TW), Pu; Han-Ping (Taichung, TW), Pan; Hsin-Yu (Taipei, TW), Liu; Ming-Kai (Hsinchu, TW), Ko; Ting-Chu (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 1000008781163

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 17/872033

Filed: July 25, 2022

Prior Publication Data

Document Identifier

Publication Date

US 20220359347 A1

Nov. 10, 2022

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L23/00** (20060101); **G02B6/30** (20060101); **H01L21/48** (20060101); **H01L21/56** (20060101); **H01L23/31** (20060101); **H01L23/367** (20060101); **H01L23/48** (20060101); **H01L23/538** (20060101); **H01L25/065** (20230101); **H01L25/18** (20230101)

U.S. Cl.:

CPC **H01L23/481** (20130101); **H01L21/4875** (20130101); **H01L21/56** (20130101); **H01L23/3107** (20130101); **H01L23/367** (20130101); **H01L25/0657** (20130101); **H01L2225/06548** (20130101)

Field of Classification Search

CPC: H01L (2225/06503-06596); H01L (25/117); H01L (25/0756); H01L (25/074); H01L (25/0657); H01L (25/043); H01L (23/34-4735); H01L (23/36); H01L (23/3731); H01L (23/3738); H01L (23/42); H01L (23/4334); H01L (23/5385); H01L (23/3128); H01L (23/4275); H01L (23/49827); H01L (24/00); H01L (24/09); H01L (24/81); H01L (25/50)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9368479	12/2015	Katkar	N/A	H01L 23/5386
9583415	12/2016	Yu	N/A	H01L 23/36
9735131	12/2016	Su	N/A	H01L 25/50
9780079	12/2016	Li	N/A	H01L 25/50
10770430	12/2019	Kim	N/A	H01L 25/50
10790162	12/2019	Tsai	N/A	H01L 23/5389
10818651	12/2019	Hsu	N/A	H01L 24/49
11062971	12/2020	Hung	N/A	H01L 23/5384
2006/0197209	12/2005	Choi	257/E21.505	H01L 25/162
2007/0023889	12/2006	Salmon	257/E23.072	G02B 6/43
2010/0052111	12/2009	Urakawa	257/621	H01L 25/18
2011/0001148	12/2010	Sun	257/E33.059	H01L 33/60
2011/0186990	12/2010	Mawatari	257/737	H01L 23/481
2011/0215457	12/2010	Park	257/E23.101	H01L 25/50
2012/0025388	12/2011	Law	257/773	H01L 25/0657
2013/0119528	12/2012	Groothuis	257/777	H01L 23/3675
2013/0277821	12/2012	Lundberg	257/713	H01L 23/3677
2014/0084444	12/2013	Lin	438/122	H01L 25/0657
2015/0035134	12/2014	Hung	257/712	H01L 24/92
2015/0155011	12/2014	Schenck	365/51	G11C 5/063
2015/0155218	12/2014	Hung	257/713	H01L 23/3677
2015/0170991	12/2014	Li	438/109	H01L 23/4334

2015/0348956	12/2014	Groothuis	438/107	H01L 23/3677
2015/0371971	12/2014	Yokoyama	257/738	H01L 25/0657
2016/0013115	12/2015	Vadhavkar	257/713	H01L 23/3675
2016/0013173	12/2015	Vadhavkar	438/109	H01L 23/3675
2016/0049349	12/2015	Lane	257/777	H01L 23/3677
2016/0093598	12/2015	Jo	257/713	H01L 23/36
2016/0322340	12/2015	Li	N/A	H01L 25/0657
2017/0229439	12/2016	Vadhavkar	N/A	H01L 24/13
2018/0108592	12/2017	Hembree	N/A	H01L 23/367
2019/0006549	12/2018	Yim	N/A	H01L 23/49827
2020/0176384	12/2019	Wu	N/A	H01L 25/0655
2020/0365544	12/2019	Chen	N/A	H01L 25/18
2020/0381397	12/2019	Yu	N/A	H01L 24/08
2021/0202354	12/2020	Chuang	N/A	H01L 21/4875
2021/0225790	12/2020	Chen	N/A	H01L 24/32

Primary Examiner: Ojha; Ajay

Assistant Examiner: Chiu; Tsz K

Attorney, Agent or Firm: JCIPRNET

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a continuation application of and claims the priority benefit of U.S. patent application Ser. No. 16/897,300, filed on Jun. 10, 2020 and now allowed. The prior application Ser. No. 16/897,300 claims the priority benefit of U.S. provisional application Ser. No. 62/953,502, filed on Dec. 25, 2019. The entirety of each of the above-mentioned patent applications is hereby incorporated by reference herein and made a part of this specification.

BACKGROUND

(1) As size downscaling and operation speed increasing, the thermal dissipation for highly integrated semiconductor packaging is an important issue and has great impact on the performance of the semiconductor devices.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 is a schematic top view of a memory device according to some embodiments of the present disclosure.

(3) FIG. 2 to FIG. 13 are schematic cross-sectional views of structures produced at various stages of a manufacturing method of a memory device according to some embodiments of the present disclosure.

(4) FIG. 14 is a schematic top view showing an exemplary intermediate structure of a memory

device according to some embodiments of the present disclosure.

(5) FIG. 15 to FIG. 17 are enlarged schematic cross-sectional views showing a portion of the exemplary structure(s) of a memory device according to embodiments of the present disclosure.

(6) FIG. 18, FIG. 19 and FIG. 20 are schematic top and cross-sectional views showing the exemplary structure of a memory device according to some embodiments of the present disclosure.

(7) FIG. 21 is a schematic top view of a memory device according to some embodiments of the present disclosure.

(8) FIG. 22 and FIG. 23 are enlarged schematic cross-sectional views showing a portion of the exemplary structure(s) of a memory device according to embodiments of the present disclosure.

DETAILED DESCRIPTION

(9) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(10) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(11) Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

(12) FIG. 1 is a schematic top view of a memory device according to some embodiments of the present disclosure, having I-I' and II-II' cross-section lines in the X-direction and Y-direction. FIG. 2 to FIG. 13 are schematic cross-sectional views of structures produced at various stages of a manufacturing method of a memory device according to some embodiments of the present disclosure. FIG. 1 show the exemplary structure of a memory device produced through the manufacturing method shown from FIG. 2 to FIG. 13. FIG. 2, FIG. 4, FIG. 6, FIG. 8, FIG. 10 and FIG. 12 show the schematic cross-sectional views along the I-I' cross-section line, while FIG. 3, FIG. 5, FIG. 7, FIG. 9, FIG. 11 and FIG. 13 show the schematic cross-sectional views along the II-II' cross-section line. The schematic cross-sectional views respectively along the I-I' and II-II' cross-section lines of the structure at the same stage of the manufacturing method are shown as pairs: FIG. 2 and FIG. 3, FIG. 4 and FIG. 5, FIG. 6 and FIG. 7, FIG. 8 and FIG. 9, FIG. 10 and FIG. 11 as well as FIG. 12 and FIG. 13. FIG. 14 is a schematic top view of the exemplary molded structure as shown in FIG. 4 and FIG. 5.

(13) Referring to FIG. 1, FIG. 2 and FIG. 3, a carrier C is provided. In some embodiments, the

carrier C is a glass substrate, a metal plate, a plastic supporting board or the like, but other suitable substrate materials may be used as long as the materials are able to withstand the subsequent steps of the process. In some embodiments, a de-bonding layer (not shown) is provided on the carrier C to facilitate peeling the carrier C away from the structure when required by the manufacturing process. In some embodiments, the de-bonding layer may include a light-to-heat conversion (LTHC) release layer.

(14) In some embodiments, referring to FIG. 2 and FIG. 3, semiconductor chips or dies **110** are provided on the carrier C. Herein, semiconductor chips and semiconductor dies may be used interchangeably and refer to dies or chips having semiconductor integrated circuits (ICs), or hybrid integrated circuits with passive components. In some embodiments, the semiconductor chips **110** are placed onto the carrier C through a pick-and-place method and are fixed to the carrier C through a die attach film (DAF) **105**. In some embodiments, two semiconductor chips **110** are arranged as one packaging unit PU using wafer-level packaging technology. Even though only two semiconductor chips **110** are presented in FIG. 3 for illustrative purposes, less or more than two semiconductor chips **110** may be provided within the packaging unit on the carrier C. In some embodiments, an individual semiconductor chip **110** includes a semiconductor substrate **111**, contacts **113**, and a protective layer **115**. For example, the contacts **113** are formed at a top surface of the semiconductor substrate **111**, and the protective layer **115** covers the top surface of the semiconductor substrate **111** but exposes the contacts **113**.

(15) In some embodiments, the semiconductor substrate **111** is made of elemental semiconductor materials, such as crystalline silicon, diamond, or germanium; compound semiconductor materials such as silicon carbide, gallium arsenic, indium arsenide, or indium phosphide or alloy semiconductor materials such as silicon germanium, silicon germanium carbide, gallium arsenic phosphide, or gallium indium phosphide. In some embodiments, the material of the contacts **113** includes copper, copper alloys, or other conductive materials, and may be formed by deposition, plating, or other suitable techniques. The protective layer **115** may be a single layer or a multi-layered structure, and may include silicon oxide, silicon nitride, silicon oxy-nitride, other suitable dielectric materials, or combinations thereof.

(16) In some embodiments the semiconductor chips **110** are placed over the carrier C with their top surfaces facing away from the carrier C and their bottom surfaces are attached to the carrier C through the DAF **105**. In some embodiments, the semiconductor chips **110** are memory chips or include memory chips or dies, and are configured as dynamic random access memories (DRAMs), resistive random access memories (RRAMs), static random access memories (SRAMs), magnetoresistive random access memories (MRAMs), ferroelectric random access memories (FRAMs), or the like.

(17) In some embodiments, as shown in FIG. 2 and FIG. 3, the two semiconductor chips **110** (as a pair) are disposed on the carrier C side-by-side with a gap G1 there-between, and the two semiconductor chips **110** (shown in dotted lines in FIG. 1) are spaced apart with a distance D1 (in the Y-direction) ranging from about 60 microns to about 100 microns. The distance D1 is measured between two facing sides of the semiconductor chips **110**. In some embodiments, the semiconductor chips **110** have a rectangular shape and the semiconductor chips **110** are arranged with the long sides in parallel with each other.

(18) Referring to FIG. 2, in some embodiments, thermally conductive walls **120** are provided on the carrier C beside the semiconductor chips **110** and there are gaps G2 between the semiconductor chips **110** and the thermally conductive walls **120**. Taking the rectangular shaped chips as an example, the thermally conductive walls **120** are located at the opposite short sides (non-facing sides) of the rectangular chips **110**, and are spaced apart from the semiconductor chips **110** with a distance D2 (in the X-direction) ranging from about 60 microns to about 100 microns. Referring to the top view shown in FIG. 14, in one embodiment, the thermally conductive walls **120** have a rectangular shape and are aligned as a single line beside the pair of the semiconductor chips **110**.

From the top view of FIG. 14, except for the two long sides of the semiconductor chips **110** facing each other (with distance D1) being the facing sides, the other sides of the group of semiconductor chips **110** are considered as non-facing sides. The thermally conductive walls **120** are arranged at non-facing sides of the pair (or the group) of the semiconductor chips **110**. However, it is understood that the thermally conductive walls **120** may be arranged as multiple lines, columns, rows or even as arrays at two opposite sides of chips or surrounding the chips, depending on the thermal dissipation requirements. In one embodiment, the thermally conductive walls **120** are of substantially the same size or dimensions and have a length (Y-direction) of about 200 microns. In some embodiments, the thermally conductive walls **120** standing on the carrier C with a height higher than or substantially equivalent to the height (the thickness direction) of the semiconductor chips **110**. In some embodiments, the thermally conductive walls **120** are separate from one another and spaced apart from the adjacent thermally conductive wall(s) **120** with a uniform spacing.

(19) In some embodiments, the material of the thermally conductive walls **120** includes metals, metal alloys or other thermally conductive materials. In some embodiments, the thermally conductive wall **120** is a metal or metallic block. In some embodiments, the thermally conductive walls **120** are blocks made of copper or copper alloys by plating or deposition. In some embodiments, the formation of the thermally conductive walls **120** includes forming a mask pattern (not shown) with openings, then forming a metallic material (not shown) filling up the openings by electroplating or deposition, and removing the mask pattern to form the thermally conductive walls **120**. In some embodiments, the thermally conductive walls **120** are formed from a conductive paste including metallic particles such as a silver paste. In some alternative embodiments, a solder-based paste (i.e. eutectic solder containing lead or lead-free) is used to form the thermally conductive walls **120**. In some embodiments, the silver paste or the solder-based paste may be applied on the carrier C via dispenser, screen printing or other suitable techniques, and followed by curing or reflow. In some embodiments, the thermally conductive wall **120** has a thermal conductivity equivalent to or larger than 70 watts per meter-kelvin (W/(m.Math.K)). The material of the thermally conductive walls **120** may be chosen based on the process compatibility, the considerations of desired performances and production costs.

(20) Referring to FIG. 4, FIG. 5 and FIG. 14, an encapsulant **130** is formed over the carrier C, covering the semiconductor chips **110** and thermally conductive walls **120**. In some embodiments, as seen in FIG. 4 and FIG. 5, the encapsulant **130** at least covers the sidewalls of the semiconductor chips **110** and the sidewalls of the thermally conductive walls **120** and fills up the gaps G1 between the semiconductor chips **110** and the gaps G2 between the thermally conductive walls **120** and the semiconductor chips **110**. In some embodiments, the encapsulant **130** is formed by forming an encapsulating material (not shown) over the carrier C fully covering the semiconductor chips **110** and the thermally conductive walls **120** and then planarizing the encapsulating material. In some embodiments, the encapsulating material of the encapsulant **130** includes epoxy resins, phenolic resins or other curable resin materials. In some embodiments, the encapsulating material may further include fillers. In some embodiments, the encapsulant **130** is formed through an over-molding process. In some embodiments, the encapsulant **130** is formed through a compression molding process. In some embodiments, the thermal conductivity of the thermally conductive walls **120** is at least larger than the thermal conductivity of the encapsulant **130**. In some embodiments, the thermally conductive walls **120** has a thermal conductivity about 60~70 times higher than the thermal conductivity of the encapsulant **130**.

(21) Referring to FIG. 4 and FIG. 5, in some embodiments, the encapsulant **130** is formed following, for example, a planarization process, so that the top surface **130t** of the encapsulant **130** is levelled with and coplanar with the top surfaces of the thermally conductive walls **120** and the semiconductor chips **110** (with the contacts **113** of the semiconductor chips **110** exposed). In some embodiments, the planarization process includes performing a mechanical grinding process and/or a chemical mechanical polishing (CMP) process. Following planarization, the contacts **113** of the

semiconductor chips **110** are exposed and available for electrically connecting the semiconductor chips **110** to subsequently formed components or elements. In some embodiments, the top surfaces **110t** of the semiconductor chips **110** are referred as active surfaces of the semiconductor chips **110**. (22) In some embodiments, through the formation of the encapsulant **130**, the semiconductor chips **110** and the thermally conductive walls beside the chips **110** are all molded into a molded structure **10** (similar to a reconstructed wafer structure), and the molded structure **10** includes a plurality of packaging units PU. In other words, the exemplary processes may be performed at a reconstructed wafer level, so that the plurality of units PU are processed in the form of a reconstructed wafer. In the cross-sectional views shown from FIG. 2 to FIG. 13, one packaging unit PU is shown for simplicity, but the disclosure is not limited by the embodiments or figures shown herein. In some embodiments, the semiconductor chips **110**, the thermally conductive walls **120** disposed beside the chips **110**, and the encapsulant **130** which laterally surrounds the semiconductor chips **110** and the thermally conductive walls **120** are considered a first tier portion of the molded structure **10**.

(23) Referring to FIG. 6 and FIG. 7, in some embodiments, a redistribution structure **140** is formed on the first tier portion of the molded structure **10**. In some embodiments, as seen in FIG. 6 and FIG. 7, the redistribution structure **140** includes a dielectric layer **142** and a redistribution conductive layer **144**. For simplicity, the dielectric layer **142** is illustrated as a single dielectric layer and the redistribution conductive layer **144** is illustrated to include the conductive redistribution patterns embedded in the dielectric layer **142**. Nevertheless, from the perspective of the manufacturing process, the redistribution structure **140** may include multiple layers of redistribution patterns, which are insulated by one or more dielectric layers. The redistribution patterns may include circuit lines extending horizontally and conductive vias extending vertically through the dielectric layers to establish electrical connection between the layers of the redistribution patterns. In some embodiments, the redistribution conductive layer **144** includes first redistribution patterns **144A** that are electrically connected with the underlying semiconductor chips **110** and second redistribution patterns **144B** that are physically connected to the underlying thermally conductive walls **120**. In some embodiments, the first redistribution patterns **144A** may extend over and beyond the spans of the semiconductor chips **110**, while the second redistribution patterns **144B** are mainly located right above the thermally conductive walls **120**. That is, vertical projections of the second redistribution patterns **144B** fall on the thermally conductive walls **120** rather than on the semiconductor chips **110**. In some embodiments, the first redistribution patterns **144A** may be electrically interconnected but the first redistribution patterns **144A** are electrically isolated from the second redistribution patterns **144B**. As the redistribution structure **140** is formed on the first tier portion of the molded structure **10**, the redistribution structure **140** is also illustrated as the first tier redistribution layer (RDL) structure and may be considered as part of the first tier **10A** of the molded structure **10**.

(24) In some embodiments, the redistribution conductive layer **144** is made of a metal or metallic material, such as aluminum, titanium, copper, nickel, tungsten, silver, gold, combinations or alloys thereof. In certain embodiments, the material of the redistribution conductive layer **144** includes copper or copper alloys. The redistribution conductive layer **144** may be formed by, for example, electroplating, deposition, and/or photolithography and etching. In some embodiments, the material of the dielectric layer **142** includes polyimide, benzocyclobutene (BCB), polybenzooxazole (PBO), or any other suitable resin-based dielectric material. The dielectric layer **142**, for example, may be formed by suitable fabrication techniques such as spin-on coating, chemical vapor deposition (CVD) such as plasma-enhanced chemical vapor deposition (PECVD), or the like. It should be noted that the number of layers of redistribution patterns in the redistribution conductive layer **144** and the number of the dielectric layers in the dielectric layer **142** described herein are merely for illustrative purposes, and the disclosure is not limited thereto.

(25) Referring to FIG. 8 and FIG. 9, in some embodiments, following the formation of the first tier **10A**, similar processes and methods for forming the first tier **10A** are performed in sequence and

repeatedly to form the second tier **10B**, third tier **10C** and fourth tier **10D** of the molded structure **10**. After forming the redistribution structure **140**, individual thermally conductive vias (TCVs) **220** and individual through insulator vias (TIVs) **220A** are formed on the redistribution structure **140**. In some embodiments, the TIVs **220A** are of substantially the same dimensions, and the TCVs **220** are of substantially the same dimensions. In one embodiment, the TCVs **220** have a critical dimension substantially the same as that of the TIVs **220A**. In some embodiments, the TIVs **220A** and the TCVs **220** may have substantially the same height (in thickness direction) but are different in sizes (with different diameters). In one embodiment, the TCVs **220** have a critical dimension larger than that of the TIVs **220A**. In some embodiments, the TCVs **220** are formed on and connected with the second redistribution patterns **144B**. In some embodiments, the TCVs **220** directly contact the second redistribution patterns **144B**, and the TCVs **220** are connected to the underlying thermally conductive walls **120** through the second redistribution patterns **144B**. In some embodiments, the TIVs **220A** are formed on and connected with the first redistribution patterns **144A**. In some embodiments, as seen in FIG. **1**, FIG. **3** and FIG. **9**, the TIVs **220A** are separate from one another and are arranged as one or more arrays respectively located alongside both sides of the gap **G1**. Later, the semiconductor chips **210** are disposed on the redistribution structure **140**. As seen in FIG. **9**, within one packaging unit PU, two semiconductor chips **210** are provided as a pair spaced apart from each other with a distance **D3** (in the Y-direction), and the pair of semiconductor chips **210** are spaced apart from the TIVs **220A** and are located beside the arrays of the TIVs **220A**. The TIVs **220A** are respectively located at two facing sides of the semiconductor chips **210**, located between the semiconductor chips **210** and are spaced apart from the semiconductor chips **210**. Taking the rectangular shaped chips as an example, the TCVs **220** are located at the opposite short sides of the rectangular chips **210**, and are spaced apart from the semiconductor chips **210**.

(26) For example, when the semiconductor chips **210** and the semiconductor chips **110** are of about the same dimensions/sizes, and the distance **D3** in the Y-direction is larger than the distance **D1**, from the top view, the X-direction extending sides of the semiconductor chips **210** are not vertically aligned with the X-direction extending sides of the semiconductor chips **110**, but the Y-direction extending sides of the semiconductor chips **210** are vertically aligned with the Y-direction extending sides of the semiconductor chips **110**. In other words, the vertical projections of the TIVs **220A** fall on the spans of the underlying semiconductor chips **110**, not overlapped with the gap **G1**. In some embodiments, vertical projections of the TCVs **220** fall on the spans of the corresponding thermally conductive walls **120**. In some embodiments, the semiconductor chips **210** have a rectangular shape and the semiconductor chips **210** are arranged with the long sides in parallel with each other. Similarly, the semiconductor chips **210** are memory chips or include memory chips or dies. In some embodiments, the semiconductor chips **210** have substantially the same functions as the semiconductor chips **110**. In some embodiments, the semiconductor chips **210** may have different functions from the semiconductor chips **110**. The areas circled by the dotted lines and labeled as CP in FIG. **1** refer to the regions where the contact pads of the semiconductor chips are located.

(27) In some embodiments, as seen in FIG. **8** and FIG. **9**, multiple TIVs **220A** that are located between the semiconductor chips **210** are electrically connected with the underlying semiconductor chips **110** through the first redistribution patterns **144A**. In some embodiments, as seen in FIG. **9**, the number of TIVs **220A** in a row may be determined based on the spacing there-between, the distance **D3** between the semiconductor chips **210**, and the gap **G1** between the semiconductor chips **110** in the first tier **10A**. As seen in FIG. **1**, multiple TIVs (e.g. **420A**) may be disposed as arrays according to design and routing requirements. On the other hand, multiple TCVs **220** that are located beside the semiconductor chips **210** are thermally connected with the underlying thermally conductive walls **120** through the second redistribution patterns **144B**. In some embodiments, as seen in FIG. **8**, the number of TCVs **220** in a row may be determined based on the spacing there-between, the available distance between the semiconductor chips **210** respectively in

adjacent packaging units, and the size of the thermally conductive wall **120** in the first tier **10A**. In general, the TCVs **220** are connected to the underlying thermally conductive walls **120** in a multiple-to-one fashion (e.g. multiple TCVs **220** connected to one thermally conductive wall **120**). It should be noted that the number of TIVs or TCVs described herein are merely for illustrative purposes, and may be varied depending on the design of redistribution patterns in the redistribution conductive layer **144**, but the disclosure is not limited thereto.

(28) In some embodiments, from the perspective of the manufacturing process, the TIVs **220A** and the TCVs **220** are formed from substantially the same material through the same manufacturing process. In other words, the TCVs **220** are fabricated along with the TIVs **220A** through the manufacturing process of the TIVs **220A**. For example, the TIVs **220A** and TCVs **220** are formed by conformally forming a seed layer (not shown) by sputtering over the redistribution structure **140**, forming a mask (not shown) with openings exposing the intended locations for the subsequently formed TIVs and TCVs and then forming a metal/metallic material (not shown) by plating to fill up the openings. In the drawings of the disclosure, the seed layer may be omitted for simplicity. Alternatively, the TIVs and TCVs may be prefabricated (e.g., pre-fabricated copper posts), and provided on the redistribution structure **140** at pre-determined locations. It is understood that the TIVs and TCVs may be formed through other available semiconductor manufacturing processes, and the disclosure is not limited by the embodiments described herein. In some embodiments, the TIVs **220A** and the TCVs **220** are made of a metal or metallic material, such as aluminum, titanium, copper, nickel, tungsten, silver, gold, combinations or alloys thereof. In certain embodiments, the material of the TIVs **220A** and the TCVs **220** includes copper or copper alloys. In some embodiments, the material of the thermally conductive wall **120** is substantially the same as the material of the TCVs **220**. In some other embodiments, the material of the thermally conductive wall **120** is different from the material of the TCVs **220**.

(29) Referring to FIG. **8** and FIG. **9**, an encapsulant **230** is formed on the redistribution structure **140** laterally wrapping the semiconductor chips **210**, the TCVs **220** and the TIVs **220A**. In some embodiments, the encapsulant **230** extends in between the semiconductor chips **210**, and in between adjacent TCVs **220**, adjacent TIVs **220A** and in between the chips **210** and the TCVs **220** and TIVs **220A**. The material and the manufacturing process of the encapsulant **230** may be similar to those described above for the encapsulant **130**. Later, a redistribution structure **240** is formed over the encapsulant **230**, the semiconductor chips **210**, the TCVs **220** and the TIVs **220A**. In some embodiments, the semiconductor chips **210**, the TIVs **220A**, the TCVs **220**, the encapsulant **230** and the redistribution structure **240** formed thereon together form a second tier **10B** of the molded structure **10**. Similarly, the redistribution structure **240** includes a dielectric layer **242** and a redistribution conductive layer **244**. First redistribution patterns **244A** and second redistribution patterns **244B** of the redistribution conductive layer **244** are embedded in the dielectric layer **242**. In some embodiments, the first redistribution patterns **244A** are physically and electrically connected with the semiconductor chips **210** and with the TIVs **220A**, and are electrically connected with the semiconductor chips **110** through the first redistribution patterns **144A**. The TIVs **220A** establish electrical connection between the redistribution structures **140** and **240** and, consequently, between the semiconductor chips **110** and **210**. In some embodiments, the second redistribution patterns **244B** are physically connected with the TCVs **220**, which are further connected with the thermally conductive walls **120** through the second redistribution patterns **144B**. In some embodiments, the thermal conductivity of the TCVs **220** is at least larger than the thermal conductivity of the encapsulant **230**. In some embodiments, the first redistribution patterns **244A** may be electrically interconnected but the first redistribution patterns **244A** are electrically isolated from the second redistribution patterns **244B**.

(30) Referring to FIG. **8** and FIG. **9**, the third tier **10C** and the fourth tier **10D** (or additional tiers) may be sequentially formed on the second tier **10B** following similar manufacturing process steps. In some embodiments, TCVs **320** and TIVs **320A** are provided on the redistributions structure **240**

in areas respectively overlying the TCVs **220** (right above thermally conductive walls **120**) and the TIVs **220A**. Semiconductor chips **310** are disposed beside the TIVs **320A**, and vertically aligned with the semiconductor chips **210**. After forming an encapsulant **330** laterally wrapping the TIVs **320A**, the semiconductor chips **320** and the TCVs **320**, a redistribution structure **340** is formed thereon and the third tier **10C** is formed. The TIVs **320A** electrically connect the redistribution conductive layers **240** and **340**. Similarly, TCVs **420**, TIVs **420A** and semiconductor chips **410** are provided on the redistribution structure **340** and laterally encapsulated in an encapsulant **430** and a redistribution structure **440** is formed thereon, so as to form the fourth tier **10D**. In some embodiments, the TIVs **420A** are vertically aligned with the TIVs **320A** and **220A**, and the semiconductor chips **410** are vertically stacked with the semiconductor chips **310** and **210**. The semiconductor chips **410** are electrically connected with the TIVs **420A** through first redistribution patterns **444A** of the redistribution structure **440**. The TIVs **420A** electrically connect the redistribution conductive layers **340** and **440**. In some embodiments, the TCVs **420** are vertically aligned with the TCVs **320** and **220**. The TCVs **420**, **320**, **220** and the underlying thermally conductive walls **120** vertically stacked with one another form thermal paths for improving heat dissipation.

(31) Referring to FIG. **8** and FIG. **9**, in some embodiments, the semiconductor chips **410**, **310** in the third tier **10C** and fourth tier **10D** may be arranged in pairs in correspondence of the semiconductor chips **210** in the second tier **10B**. That is, the semiconductor chips **410** of the fourth tier **10D** may be vertically aligned with the semiconductor chips **310** of the third tier **10C** and with the semiconductor chips **210** of the second tier **10B**. From FIG. **1** and FIG. **9**, the semiconductor chips **210** of the second tier **10B** at least partially overlap with corresponding underlying semiconductor chips **110** of the first tier **10A**. Similarly, the semiconductor chips **410**, **310** are memory chips or include memory chips or dies. In some embodiments, the semiconductor chips **410**, **310** have substantially the same functions as the semiconductor chips **210**. In some embodiments, the semiconductor chips **410**, **310** may have different functions from the semiconductor chips **210**.

(32) In some embodiments, in FIG. **8** and FIG. **9**, connectors **450** are formed on and connected with the redistribution structure **440**. In some embodiments, under-bump metallurgies may be optionally formed below the connectors **450**. The connectors **450** may include ball grid array (BGA) connectors, metal pillars, metal pillars with solder thereon, controlled collapse chip connection (C4) bumps, micro bump, a combination thereof, or the like. In some embodiments, the connectors **450** are micro bumps.

(33) Similar to the previous tiers, the redistribution structure **440** includes first redistribution patterns **444A** and second redistribution patterns **444B**, and the first redistribution patterns **444A** may be electrically interconnected but the second redistribution patterns **444B** are electrically isolated from the first redistribution patterns **444A**. Some of the connectors **450** are physically and electrically connected with first redistribution patterns **444A** (connected with TIVs **420A**), and function as electrical terminals for the underlying semiconductor chips. That is, the semiconductor chips **110**, **210**, **310**, **410** in the packaging unit PU are electrically connected via the TIVs **220A**, **320A**, **420A** along with the redistribution structures **140**, **240**, **340**, **440**, and some connectors **450** that are connected to the first redistribution patterns **444A** are electrically connected to the semiconductor chips **110**, **210**, **310**, **410** through the TIVs **420A**, **320A**, **220A** as well as the redistribution structures **140**, **240**, **340**, **440**.

(34) In the embodiments, the TIVs **220A**, **320A**, **420A** located between the semiconductor chips mainly function for electrical connection. However, it is understood that the top tier semiconductor chips **110** and the TIVs **220A**, **320A**, **420A** located under the chips **110** together also assist heat dissipation for the regions situated between the semiconductor chips under certain circumstances.

(35) On the other hand, some of the connectors **450** that are connected with the second redistribution patterns **444B** (connected with TCVs **420**) function as part of the thermal paths,

rather than for electrical connection. In some embodiments, in FIG. 8 and FIG. 9, the vertically connected structures, including TCVs **420**, **320**, **220** and the underlying thermally conductive walls **120**, the second redistribution patterns there-between and the connectors **450** that are located on the second redistribution patterns, form thermal paths for assisting heat dissipation. The thermal path structures (vertically connected structures mainly including TCVs **420**, **320**, **220** and the underlying thermally conductive walls **120**) are electrically isolated from the semiconductor chips since they are connected through the second redistribution patterns in the redistribution structure of each tier, and the second redistribution patterns are not electrically connected with the first redistribution patterns in the same redistribution structure and the semiconductor chips.

(36) In some embodiments, referring to FIG. 10 and FIG. 11, after formation of the connectors **450**, by cutting through the encapsulants **130**, **230**, **330**, **430**, the molded structure **10** may be singulated or diced into individual packaging units PU. After the singulation process, the TCVs **420**, **320**, **220** and the thermally conductive walls **120** are located in the peripheral region of the packaging unit PU. In some embodiments, after removing the carrier C, the packaging unit PU is obtained. The top view of FIG. 1 schematically shows the relative positional relationships for the TIVs **420A**, TCVs **420** and semiconductor chips **410**, **110** in the singulated packaging unit PU before it is flipped, and certain redistribution structures and connectors are omitted for illustrative purposes. In some embodiments, after removing the carrier C, in FIG. 10 and FIG. 11, the exposed surfaces (top surfaces) of the thermally conductive walls **120** are substantially coplanar with and levelled with the exposed surface of the encapsulant **130**. In some embodiments, the packaging unit PU includes multiple tiers **10A-10D** of stacked semiconductor chips **110**, **210**, **310**, **410** encapsulated by respective encapsulants **130**, **230**, **330**, **430**, and redistribution structures **140**, **240**, **340**, **440** for electrically connecting the semiconductor chips **110**, **210**, **310**, **410**. In some embodiments, when one or more of the stacked semiconductor chips **110**, **210**, **310**, **410** are or include memory chips, the packaging unit PU may be referred to as a memory cube. In some embodiments, the memory cube(s) may function as a memory device.

(37) In some embodiments, the semiconductor chips **210**, **310**, **410** may be disposed in aligned locations of the corresponding tiers and the semiconductor chips **110** may be disposed in locations vertically partial-overlapped with those of the corresponding semiconductor chips **210**, **310**, **410**. The packaging unit PU is then flipped (turned upside down) and placed on a base chip **510**. In some embodiments, referring to FIG. 10 and FIG. 11, the packaging unit PU is connected to the base chip **510** through the connectors **450** bonded to the contact pads of the base chip **510**, and an underfill **505** is formed between the packaging unit PU and the base chip **510** and between the connectors **450**. The underfill **505** may physically protect the connection between the connectors **450** and the contact pads of the base chip **510**. Referring to FIG. 10 and FIG. 11, in some embodiments, the base chip **510** is or includes a logic chip, such as a controller chip or a chip or die with processing circuits. It is understood that one, two, three, four or more memory cubes may be mounted and bonded to the base chip/die, and the disclosure is not limited by the drawings. In some embodiments, the base chip **510** includes a semiconductor substrate **511**, through substrate vias (TSVs) **512**, and interconnection layers **514**. The base chip **510** has a larger footprint than the packaging unit PU (i.e. memory cube). Conductive terminals **550** are provided on the bottom surface of the base chip **510** for further electrical connection. In some embodiments, under-bump metallurgies may be optionally formed below the conductive terminals **550**. The conductive terminals **550** may include ball grid array (BGA) connectors, metal pillars, metal pillars with solder thereon, controlled collapse chip connection (C4) bumps, micro bump, a combination thereof, or the like. In some embodiments, the conductive terminals **550** are C4 bumps. In some embodiments, the TSVs **512** are arranged in a region of the base chip **510** corresponding to the region where the TIVs **220A**, **320A**, **420A** are located, for electrical connection. The semiconductor chips in the packaging unit PU are electrically connected with the base chip **510** through its contact pads and the connectors **450** there-between, and are further electrically connected with the conductive

terminals **550** through the TSVs **512** and the interconnection layers **514**. On the other hand, the thermally conductive walls **120** and the underlying TCVs **220, 320, 420** are thermally connected with the base chip **510** through its contact pads and the connectors **450** there-between, but are not electrically connected with the base chip **510**. The thermal path structures (the vertically connected structures mainly including TCVs **420, 320, 220** and the underlying thermally conductive walls **120**) are electrically isolated from the semiconductor chips **110, 210, 310, 410** of the memory cube as well as the base chip **510**.

(38) As the thermal path structures vertically extend through the memory cube and are connected with the base chip, heat generated in the base chip during operation may be dissipate through the thermal paths (through the thermal path structures) to the upper or top tier, or then dissipated to the outer or external environment.

(39) In some embodiments, referring to FIG. **12** and FIG. **13**, the memory device **50** is completed by further forming a molding compound **530** to laterally wrap the packaging unit PU bonded to the base chip **510**. In some embodiments, the material of the molding compound **530** includes epoxy resins, phenolic resins or other curable resin materials, and may further include fillers. In some embodiments, the molding compound **530** is formed through an over-molding process. In some embodiments, the molding compound **530** is formed through a compression molding process. In one embodiment, the material of the molding compound **530** is different from one of the encapsulants **130, 230, 330, 430**. In one embodiment, the material of the molding compound **530** is substantially the same as one of the encapsulants **130, 230, 330, 430**. Subsequently, the memory device **50** may be connected to a circuit substrate, a printer circuit board or even integrated with other devices via the conductive terminals **550**. Also, a heat sink or cooling module (not shown) may be optionally mounted onto the top surface of memory device **50** during applications.

(40) In some embodiments, when the memory device **50** is in operation, heat generated during operation may be more easily conveyed or dissipated through the thermal path structures constructed by the additional thermally conductive walls and TCVs arranged around and beside the semiconductor chips (arranged within the peripheral regions of the memory device). The formation of thermal paths (represented by the arrows shown in FIG. **12**) helps to guide the heat generated from the base chip through thermal paths to the upper tiers and further to the heat sink or cooling module, which significantly improves the heat dissipation of the memory device **50**. Through the formation of the thermal path structures, the thermal resistance of the memory device is at least reduced by about 2%, and may be further reduced by about 43%, depending on the hot spot locations of the base chip/die. As a result, the reliability of the memory device **50** is enhanced and the performance of the memory device **50** is boosted.

(41) FIG. **15** to FIG. **17** are enlarged schematic cross-sectional views showing a portion of the exemplary structure(s) of a memory device according to embodiments of the present disclosure.

(42) In FIG. **15**, the memory device **15** may be formed following the previous described processes, eight tiers **T1-T8** are sequentially formed, and each tier is formed with semiconductor chips **C1-C8** and redistribution structures **R1-R8**. In some embodiments, each of the tiers **T2-T8** is formed with TIVs (not shown) and TCVs **v2-v8**, but the top tier **T1** is formed with thermally conductive walls **152** rather than TCVs. The stacked tiers **T1-T8** are mounted on and bonded with the base chip **BC**. In some embodiments, the thermal path structure **150** includes at least the thermally conductive wall **152** and the underlying TCVs **v2-v8**. In FIG. **15**, the thermally conductive wall(s) **152** is connected to the underlying the TCVs **v2-v8** in a one-to-multiple fashion (e.g. one thermally conductive wall **152** connected to multiple TCVs **v2-v8**). It is understood that there are redistribution patterns located between the thermally conductive wall(s) **152** and the TCVs **v2** and between the TCVs **v2-v8**, and only the vias of the redistribution patterns are shown in the figures for simplicity. In some embodiments, the thermally conductive wall **152** has a thermal conductivity larger than that of the encapsulant **P**. In some embodiments, the thermally conductive wall **152** has a thermal conductivity equivalent to or larger than 70 watts per meter-kelvin (W/(m.Math.K)) or

larger than 140 W/(m.Math.K). In some embodiments, the thermally conductive wall **152** is a metal or metallic block. In some embodiments, the material of the thermally conductive walls **152** includes copper or copper alloys. In one embodiment, the thermally conductive wall **152** is a copper block having a thermal conductivity of about 400 watts per meter-kelvin (W/(m.Math.K)). (43) In FIG. **16**, the memory device **16** has a structure similar to the memory device **15**, except for the thermally conductive wall(s) **162** may be formed by a different process and/or with a different material. The thermally conductive wall(s) **162** are not formed during the formation of the top tier **T1** but are formed after the formation of all the tiers **T1-T8** and the removal of the carrier. After removing the carrier exposing the encapsulant **P** of the top tier **T1**, trenches are formed in the encapsulant **P** by laser drilling or etching, and then a conductive paste (not shown) is filled into the trenches to form the thermally conductive walls **162** in the top tier **T1**. In some embodiments, the conductive paste for forming the thermally conductive walls **162** includes a silver paste. In some alternative embodiments, the conductive paste for forming the thermally conductive walls **162** includes a solder-based paste (i.e. eutectic solder containing lead or lead-free). In some embodiments, the thermal path structure **160** includes at least the thermally conductive wall **162** and the underlying TCVs **v2-v8**. In some embodiments, the thermally conductive wall **162** has a thermal conductivity larger than that of the encapsulant **P**. In some embodiments, the thermally conductive wall **162** has a thermal conductivity equivalent to or larger than 70 watts per meter-kelvin (W/(m.Math.K)) or larger than 140 W/(m.Math.K). It is understood that the thermally conductive wall **162** may be formed with substantially vertical sidewalls or slightly sloped sidewalls, depending on the method used for forming the trenches.

(44) In FIG. **17**, the memory device **17** has a structure similar to the memory device **15**, except for the TCVs **v2-v8** in each of the tiers **T2-T8** are formed integrally and integrated into one block structure **Tb2-Tb8**. In FIG. **17**, the thermally conductive blocks **Tb2-Tb8** in the tiers **T2-T8** are vertically aligned. In some embodiments, the thermal path structure **170** includes at least the thermally conductive wall **172** and the underlying thermally conductive blocks **Tb2-Tb8**. In some embodiments, the thermally conductive wall(s) **172** of the top tier **T1** is connected to the underlying thermally conductive blocks **Tb2-Tb8** in the tiers **T2-T8** in a one-to-one fashion (e.g. one thermally conductive wall **172** connected to one block **Tb2-Tb8** in one tier). It is understood that there are redistribution patterns located between the thermally conductive wall(s) **172** and the block(s) **Tb2** and between the thermally conductive blocks **Tb2-Tb8** in the tiers **T2-T8**, and only the vias of the redistribution patterns are shown in the figures for simplicity. In some embodiments, the thermally conductive wall **152** has a thermal conductivity larger than that of the encapsulant **P**. In some embodiments, the thermally conductive wall **152** has a thermal conductivity equivalent to or larger than 70 watts per meter-kelvin (W/(m.Math.K)) or larger than 140 W/(m.Math.K). In some embodiments, the material of the thermally conductive blocks **Tb2-Tb8** includes a metal or a metallic material. In some embodiments, the material of the thermally conductive blocks **Tb2-Tb8** includes copper or copper alloys.

(45) FIG. **18**, FIG. **19** and FIG. **20** are schematic top and cross-sectional views showing the exemplary structure of a memory device according to some embodiments of the present disclosure. FIG. **19** and FIG. **20** show the cross-sectional views of the structure along the section lines II-II' and I-I' in FIG. **18**.

(46) Referring to FIG. **18** and FIG. **19**, in some embodiments, the memory device **19** may be formed with eight tiers **T1-T8**, and each tier is formed with semiconductor chips **C1-C8** and redistribution structures **R1-R8**. In some embodiments, each of the tiers **T2-T8** is formed with TIVs **192A** and TCVs **v2-v8**, and the top tier **T1** is formed with thermally conductive walls **192** rather than forming TCVs. The stacked tiers **T1-T8** are mounted on and bonded with the base chip **BC**. In some embodiments, the thermal path structure **190** includes at least the thermally conductive wall **192** and the underlying TCVs **v2-v8**. From the top view of FIG. **18**, it is seen that the two semiconductor chips **C1** (as a pair) of the top tier **T1** have a rectangular shape and are arranged

side-by-side with the long sides in parallel with each other. In FIG. 18, the thermally conductive walls 192 are arranged beside the semiconductor chips C1 with a distance and located at four sides of the pair of the semiconductor chips C1 (i.e. surrounding the semiconductor chips C1). Referring to the top view shown in FIG. 18, in one embodiment, the thermally conductive walls 192 have a rectangular shape and are aligned as a single line beside the pair of the semiconductor chips C1. However, it is understood that the thermally conductive walls 120 may be arranged as multiple lines, columns, rows or even as arrays at one side, two sides, three or four sides of the chips or surrounding the groups of chips, depending on the thermal dissipation requirements. In one embodiment, the thermally conductive walls 192 are of substantially the same size or dimensions, and the thermally conductive walls 192 are separate from one another and spaced apart from the adjacent thermally conductive wall(s) 192 with a uniform spacing. From FIG. 20, it is seen that the thermally conductive walls 192 are connected with the TCVs v2-v8 in a one-to-multiple fashion, and the TCVs v2-v8 in tier T2-T8 are respectively arranged beside the semiconductor chips C2-C8 with a distance and located at four sides of the pair of the semiconductor chips C2-C8.

(47) FIG. 21 is a schematic top view of a memory device according to some embodiments of the present disclosure. FIG. 22 and FIG. 23 are enlarged schematic cross-sectional views showing a portion of the memory device according to various embodiments of the present disclosure. FIG. 22 shows the cross-sectional view of the structure along the section line I-I' in FIG. 21.

(48) Referring to FIG. 21 and FIG. 22, the memory device 21 may be formed following the previous described processes, eight tiers T1-T8 are sequentially formed, and each tier is formed with semiconductor chips C1-C8 and redistribution structures R1-R8. In some embodiments, each of the tiers T2-T8 is formed with TIVs (not shown) and TCVs v2-v8 following the previous described processes. However, for the memory device 21, the top tier T1 is provided with dummy dies DM, instead of forming thermally conductive walls or TCVs. That is, during the formation of the top tier T1, dummy dies DM are provided onto the carrier and then laterally wrapped by the encapsulant P but the thermally conductive walls are not formed. The stacked tiers T1-T8 are mounted on and bonded with the base chip BC. In some embodiments, the dummy dies DM are referred to as blocks or bars made of a semiconductor material such as a silicon chip without having active elements or passive elements therein. In some embodiments, the dummy die DM has a thermal conductivity larger than that of the encapsulant P. In some embodiments, the dummy die DM has a thermal conductivity equivalent to or larger than 140 watts per meter-kelvin ($W/(m \cdot K)$). In some embodiments, the dummy die DM is a silicon chip having a thermal conductivity of about 150 watts per meter-kelvin ($W/(m \cdot K)$). The dummy die DM may be considered as a thermally conductive block because it provides better thermal conductivity than the encapsulant P. In some embodiments, with the memory device 21, the thermal path structure 22 includes at least the dummy die DM and the underlying TCVs v2-v8. The dummy dies DM and the underlying TCVs v2-v8 vertically stacked with one another form thermal paths for improving heat dissipation. The formation of thermal paths helps to guide the heat generated from the base chip BC through thermal paths to the upper tiers and further to the outer heat sink or cooling module, which significantly improves the heat dissipation of the memory device 21. Through the formation of the thermal path structures, the thermal resistance of the memory device is at least reduced by about 4%, and may be further reduced by about 43%, depending on the hot spot locations of the base chip/die. As a result, the reliability of the memory device 21 is enhanced and the performance of the memory device 21 is boosted.

(49) From the top view of FIG. 21, it is seen that the two semiconductor chips C1 (as a pair) of the top tier T1 have a rectangular shape and are arranged side-by-side with the long sides in parallel with each other. In FIG. 21, the dummy dies DM are arranged beside the semiconductor chips C1 with a distance D4 and located at four sides of the pair of the semiconductor chips C1 (i.e. surrounding the semiconductor chips C1). In some embodiments, the distance D4 (in the X-direction) ranges from about 80 microns to about 110 microns. In some embodiments, the distance

D4 (in the X-direction) is about 100 microns. Referring to the top view shown in FIG. 21, in one embodiment, the dummy dies DM have a rectangular shape and are aligned as a single line beside four sides of the pair of the semiconductor chips C1. However, it is understood that the dummy dies DM may be arranged as multiple lines, columns, rows or even as arrays at one side, two sides, three or four sides of the chips or surrounding the group of chips, depending on the thermal dissipation requirements. In one embodiment, the dummy dies DM are of substantially the same size or dimensions and have a length L_d ranging from about 350 microns to about 400 microns. In one embodiment, the dummy dies DM are of substantially the same length L_d of about 380 microns. In some embodiments, the dummy dies DM have a thickness substantially equivalent to the thickness of the semiconductor chips C1. In some embodiments, the dummy dies DM are separate from one another and spaced apart from the adjacent dummy dies DM with a uniform spacing. From FIG. 22, it is seen that the dummy dies DM are connected with the TCVs v2-v8 in a one-to-multiple fashion, and the TCVs v2-v8 in tier T2-T8 are respectively arranged beside the semiconductor chips C2-C8 with a distance D5 and located at four sides of the pair of the semiconductor chips C2-C8. In some embodiments, the distance D5 (in the X-direction) ranges from about 80 microns to about 110 microns. In some embodiments, vertical projections of the TCVs v2-v8 fall within the span of the vertical projection of the dummy die DM, however the disclosure is not limited thereto. In some embodiments, as seen in FIG. 22, the span of the dummy die DM is larger than the span of the individual TCVs and larger than the total area of the spans of the TCVs in the same tier.

(50) According to some embodiments, in FIG. 23, the memory device 23 has a structure similar to the structure of the memory device 21, except that the dummy dies DM directly contact the semiconductor chips C1 in the top tier T1. In some embodiments, the dummy dies DM are provided as described in the previous embodiments but the locations of the dummy dies DM are right next to the four sides of the pair of semiconductor chips C1. In some alternative embodiments, the provided semiconductor chips C1' are pre-fabricated integrally with the extended portions Cex, and the dummy dies located right next to the chips are replaced by the extended portions Cex at the same locations. The extended portions Cex and the underlying TCVs v2-v8 together form thermal paths for improving heat dissipation. In FIG. 23, some of the TCVs v2-v8 are located outside the span of the dummy die DM or the extended portion Cex. In some embodiments, vertical projections of some of the TCVs v2-v8 fall within the span of the dummy die DM or the extended portion Cex, and vertical projections of some of the TCVs v2-v8 fall outside the span of the dummy die DM or the extended portion Cex. In some embodiments, when the extended portions Cex are integral with and parts of the semiconductor chips C1', it means that the vertical projections of the TCVs v2-v8 may also fall within the spans of the semiconductor chips C1'.

(51) In some embodiments, a memory device may include multiple tiers of vertically stacked semiconductor dies electrically connected through interposed redistribution structures and TIVs. In some embodiments, the memory device further includes additional thermal path structures located at the peripheral regions or edgings of the memory cube(s) or the memory device, and heat generated during operation may be dissipated through the thermal path structures to upper tier(s) or even to external heat sink or cooling module for better heat dissipation efficiency. In some embodiments, the thermal path structures include one or more highly conductive material (e.g., having a thermal conductivity of at least 70 W/(m.Math.K) and are arranged in the area where the heat converges, so that the thermal performance of the memory device can be enhanced, and the reliability and lifetime of the memory device can be increased. Further, the formation of the thermal path structures is compatible with the manufacturing processes for forming the memory device. For example, the thermal path structures may be formed without performing extra process steps as the TCVs may be formed along with the TIVs during the same manufacturing process. Therefore, the reliability and performance of the device or package are improved without significantly raising the production costs.

(52) In accordance with some embodiments of the disclosure, a memory device including a base chip and a memory cube mounted on and connected with the base chip is described. The memory cube includes multiple stacked tiers, and each tier of the multiple stacked tiers includes semiconductor chips laterally wrapped by an encapsulant and a redistribution structure. The semiconductor chips of the multiple stacked tiers are electrically connected with the base chip through the redistribution structures in the multiple stacked tiers. The memory cube includes a thermal path structure extending through the multiple stacked tiers and connected to the base chip. The thermal path structure has a thermal conductivity larger than that of the encapsulant. The thermal path structure is electrically isolated from the semiconductor chips in the multiple stacked tiers and the base chip.

(53) In accordance with some embodiments of the disclosure, a memory device including multiple stacked tiers, a base chip, and a molding compound is described. The base chip is located below and connected with the multiple stacked tiers through connectors there-between. The molding compound laterally wraps the multiple stacked tiers and wraps around the connectors. Each tier of the multiple stacked tiers includes semiconductor chips laterally wrapped by an encapsulant and a redistribution structure. The multiple stacked tiers include through insulator vias (TIVs) electrically connecting the semiconductor chips of the multiple stacked tiers with the base chip through the redistribution structures in the multiple stacked tiers. The multiple stacked tiers include thermal path structures located in a peripheral region at non-facing sides of the semiconductor chips and extending through the multiple stacked tiers. Each of the thermal path structures has a thermal conductivity larger than that of the encapsulant, and the thermal path structures are electrically isolated from the semiconductor chips in the multiple stacked tiers and the base chip.

(54) In accordance with some embodiments of the disclosure, a manufacturing method of a memory device is provided. The method includes at least the following steps. First semiconductor chips are disposed side by side, and thermally conductive blocks are provided at non-facing sides of the first semiconductor chips. The first semiconductor chips and the thermally conductive blocks are laterally wrapped in a first encapsulant. A first redistribution structure is formed on the first semiconductor chips, the thermally conductive blocks and the first encapsulant. Thermally conductive vias (TCVs) and through insulator vias (TIVs) are formed on the first redistribution structure. The TCVs are formed at locations right above the thermally conductive blocks and beside the first semiconductor chips, and the TIVs are formed at locations right above the first semiconductor chips. Second semiconductor chips are disposed on the first redistribution structure beside the TIVs, between the TIVs and the TCVs and between TCVs. The second semiconductor chips, the TCVs and the TIVs are laterally wrapped in a second encapsulant. A second redistribution structure is formed on the second semiconductor chips, the TCVs, the TIVs and the second encapsulant. Connectors are formed over the second redistribution structure. A base chip is electrically connected with the first and second semiconductor chips through the connectors, the TIVs and the first and second redistribution structures.

(55) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A memory device, comprising: a base chip; a memory die, mounted on and electrically connected with the base chip; and an insulating molding compound, laterally encapsulated the memory die and covering the base chip without covering sidewalls of the base chip, wherein the memory die includes multiple stacked tiers, each tier of the multiple stacked tiers includes semiconductor chips laterally wrapped by an encapsulant and a redistribution structure having first metallic redistribution patterns and second metallic redistribution patterns, and the semiconductor chips of the multiple stacked tiers are electrically connected with the base chip through the first metallic redistribution patterns of the redistribution structures in the multiple stacked tiers, and wherein the memory die includes a thermal path structure extending through the multiple stacked tiers, the thermal path structure is thermally connected with the base chip through the second metallic redistribution patterns of the redistribution structures in the multiple stacked tiers, the thermal path structure is fully laterally wrapped and fully surrounded by the encapsulants of the multiple stacked tiers and has a thermal conductivity larger than those of the encapsulants, and the thermal path structure is electrically isolated from the semiconductor chips in the multiple stacked tiers and the base chip.
2. The memory device of claim 1, wherein the multiple stacked tier includes a top tier, a middle tier underlying the top tier and a bottom tier located below the middle tier and connected to the base chip, and the thermal path structure includes a thermally conductive wall located in the top tier and thermally conductive vias (TCVs) located on the middle tier and the bottom tier.
3. The memory device of claim 2, wherein a material of the thermally conductive wall is substantially the same as a material of the TCVs.
4. The memory device of claim 2, wherein a material of the thermally conductive wall is different from a material of the TCVs.
5. The memory device of claim 1, wherein the multiple stacked tier includes a top tier, a middle tier underlying the top tier and a bottom tier located below the middle tier, the thermal path structure includes a dummy die located in the top tier and thermally conductive vias (TCVs) located on the middle tier and the bottom tier.
6. The memory device of claim 5, wherein the dummy die is made of a semiconductor material, and the semiconductor material of the dummy die is different from a material of the TCVs.
7. The memory device of claim 2, wherein the semiconductor chips in the middle tier are vertically stacked with the semiconductor chips in the bottom tier.
8. The memory device of claim 7, wherein the semiconductor chips in the top tier are spaced apart with a first distance, the semiconductor chips in the middle tier are spaced apart with a second distance, the semiconductor chips in the bottom tier are spaced apart with a third distance, the first distance is smaller than the second distance and the third distance.
9. A memory device, comprising: a base chip; multiple stacked tiers, disposed on the base chip and connected with the base chip through connectors there-between, wherein each tier of the multiple stacked tiers includes semiconductor chips laterally wrapped by an encapsulant and a redistribution structure having electro-connecting patterns and non-electro-connecting patterns, and the multiple stacked tiers include through insulator vias (TIVs) electrically connecting the semiconductor chips of the multiple stacked tiers with the base chip through the electro-connecting patterns of the redistribution structures in the multiple stacked tiers; an underfill, disposed between the multiple stacked tiers and the base chip wrapping around the connectors; and an insulating molding compound, laterally wrapping the multiple stacked tiers and covering the underfill, wherein the multiple stacked tiers include thermal path structures located in a peripheral region of the multiple stacked tiers beside the semiconductor chips and extending through the multiple stacked tiers, the thermal path structures are thermally connected through the non-electro-connecting patterns of the redistribution structures in the multiple stacked tiers to the base chip, each of the thermal path structures is fully laterally wrapped by the encapsulant and has a thermal conductivity larger than

that of the encapsulant, and the thermal path structures are electrically isolated from the semiconductor chips in the multiple stacked tiers and the base chip.

10. The memory device of claim 9, wherein the multiple stacked tier includes a top tier, a middle tier underlying the top tier and a bottom tier located below the middle tier and connected to the base chip, and each of the thermal path structures includes a thermally conductive wall located in the top tier and thermally conductive vias (TCVs) located on the middle tier and the bottom tier.

11. The memory device of claim 10, wherein a material of the thermally conductive wall includes silver paste, and a material of the TCVs includes copper or copper alloys.

12. The memory device of claim 10, wherein a material of the thermally conductive wall is substantially the same as a material of the TCVs and includes copper or copper alloys.

13. The memory device of claim 9, wherein the multiple stacked tier includes a top tier, a middle tier underlying the top tier and a bottom tier located below the middle tier and connected to the base chip, and each of the thermal path structures includes a thermally conductive wall located in the top tier and thermally conductive blocks located on the middle tier and the bottom tier.

14. The memory device of claim 13, wherein a material of the thermally conductive wall is substantially the same as a material of the thermally conductive blocks and includes copper or copper alloys.

15. The memory device of claim 9, wherein the multiple stacked tier includes a top tier, a middle tier underlying the top tier and a bottom tier located below the middle tier and connected to the base chip, and each of the thermal path structures includes a semiconductor material dummy die located in the top tier and thermally conductive vias (TCVs) located on the middle tier and the bottom tier.

16. The memory device of claim 15, wherein a material of the semiconductor material dummy die includes silicon, and a material of the TCVs includes copper or copper alloys.

17. A memory device, comprising: a bottom semiconductor chip; a memory cube, disposed on and connected with the bottom semiconductor chip through connectors there-between; and an insulating molding compound, disposed on the bottom semiconductor chip and laterally wrapping the memory cube and the connectors without covering sidewalls of the bottom semiconductor chip, wherein the memory cube includes at least a first tier, a third tier and a second tier there-between, each tier of the first tier, the second tier and the third tier includes semiconductor chips arranged side-by-side and laterally wrapped by an encapsulant and a redistribution structure having electro-connecting patterns connected with the semiconductor chips and non-electro-connecting patterns, wherein the memory cube includes a thermal path structure extending through the memory cube and connected to the bottom semiconductor chip, and the thermal path structure includes first thermally conductive vias fully surrounded by the encapsulant of the second tier and second thermally conductive vias fully surrounded by the encapsulant of the third tier, the first and second thermally conductive vias are thermally connected with the bottom semiconductor chip through the non-electro-connecting patterns of the redistribution structures of the first, second and third tiers, and wherein the thermal path structure is electrically isolated from the semiconductor chips in the first, second and third tiers and electrically isolated from the bottom semiconductor chip.

18. The memory device of claim 17, wherein the thermal path structure includes a thermally conductive wall located in the first tier.

19. The memory device of claim 18, wherein a material of the thermally conductive wall includes silver paste, copper or copper alloys, and a material of the first or second thermally conductive vias includes copper or copper alloys.

20. The memory device of claim 17, further comprising an underfill located between the memory cube and the bottom semiconductor chip and covered by the molding compound.
