

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12409609
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Bowler; John et al.

Tunable system and method for stress resolution in additive manufacturing

Abstract

Systems and methods resolve stresses in additive manufacturing. A stress resolution profile including frequency and amplitude parameters of an ultrasonic input are determined based on physical properties of the product. Successive layers of a material are added and energy is applied to incorporate the material of each layer into the product. An ultrasonic input is applied with the determined parameters to resolve stress as the product is built up. The ultrasonic input is varied as a depth of the material incorporated into the product increases.

Inventors: Bowler; John (Phoenix, AZ), Colvin; Gregory (Phoenix, AZ), Sundarraaj; Suresh (Mesa, AZ)

Applicant: HONEYWELL INTERNATIONAL INC. (Charlotte, NC)

Family ID: 75674634

Assignee: HONEYWELL INTERNATIONAL INC. (Charlotte, NC)

Appl. No.: 18/449027

Filed: August 14, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230391015 A1	Dec. 07, 2023

Related U.S. Application Data

continuation parent-doc US 16872618 20200512 US 11772330 child-doc US 18449027

Publication Classification

Int. Cl.: B29C64/393 (20170101); **B29C64/245** (20170101); **B29C64/273** (20170101)

U.S. Cl.:

CPC **B29C64/393** (20170801); **B29C64/245** (20170801); **B29C64/273** (20170801);

Field of Classification Search

CPC: B29C (64/245); B29C (64/273); B29C (64/393); B33Y (30/00); B33Y (50/02); B22F (12/90); B22F (2202/01)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8272424	12/2011	Short	N/A	N/A
10539952	12/2019	Mehr et al.	N/A	N/A
10857735	12/2019	Martin et al.	N/A	N/A
11772330	12/2022	Bowler	700/119	B33Y 50/02
2007/0040005	12/2006	Iordache et al.	N/A	N/A
2009/0049912	12/2008	Wu	N/A	N/A
2013/0101728	12/2012	Keremes et al.	N/A	N/A
2015/0041025	12/2014	Wescott et al.	N/A	N/A
2015/0314373	12/2014	Mironets et al.	N/A	N/A
2017/0059529	12/2016	Kamel et al.	N/A	N/A
2017/0087670	12/2016	Kalentics et al.	N/A	N/A
2018/0161934	12/2017	Boswell	N/A	B33Y 50/02

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
106363173	12/2016	CN	N/A
108176857	12/2017	CN	N/A
110586941	12/2018	CN	N/A
1238715	12/2001	EP	N/A
2691447	12/2018	RU	N/A
2021084162	12/2020	WO	N/A

OTHER PUBLICATIONS

Li, Qiuyan, et al., “Characterization of Materials Fabricated by Additive Manufacturing Method Using Line Focused Ultrasonic Transducer,” Nov. 2016, Downloaded from <https://asmedigitalcollection.asme.org/IMECE/proceedings-pdf/IMECE2016/50633/V009T17A010/2497897/v009t17a010-imece2016-67186.pdf> by Honeywell Aerospace user on Feb. 13, 2020. cited by applicant

Primary Examiner: Moreno Hernandez; Jerzi H

Attorney, Agent or Firm: Ingrassia Fisher & Lorenz, LLP

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION (1) This application is a continuation of and claims the benefit of co-pending U.S. patent application Ser. No. 16/872,618 filed on May 12, 2020. The disclosure of the above referenced application is incorporated herein by reference.

TECHNICAL FIELD

(1) The present invention generally relates to additive manufacturing, and more particularly relates to a tunable stress resolution approach for the accurate and quality build of complex structures by additive manufacturing.

BACKGROUND

(2) Various types of items are being created using additive manufacturing processes. Additive manufacture includes processes such as those that create a component or item by the successive addition of particles, layers or other groupings of a material onto one another. An item is generally built using a computer controlled machine that is programmed with a model which is a digital representation of the item, and includes processes such as 3-D printing. A variety of different additive manufacturing processes are used such as metal printing processes that involve directed energy deposition, laser metal powderbed fusion, material jetting, and other methods.

(3) During a typical additive manufacturing build, stresses accumulate in the product being built. As the stresses accumulate, undesirable outcomes such as distortion, imperfections, cracking, etc. may occur. The result is that the item being built may not meet dimensional or other quality requirements. This limits the use of additive manufacturing in applications where the item's structural accuracy or dimensional requirements cannot be repeatedly accomplished. For metallic components, stress relief may be attempted post-build using some form of heat treatment. Both the machines to complete the heat treatments and the time to process the parts through the heat treatment stage add both time and cost into the final parts. The stress accumulation problem has been addressed by the development of specialty software that analytically predicts the negative outcomes and adjusts/pre-compensates the build geometry design at those locations to attempt to offset the distortion or creation of such imperfections. Such software may be costly and time consuming to implement. In sum, significant additional costs may arise in additive manufacturing due to a combination of additional processing time and reduced yield. Therefore, the application of additive manufacturing as a viable alternate manufacturing option is limited.

(4) Accordingly, it is desirable to provide improved systems and methods for managing stresses in additive manufacturing to produce dimensionally accurate and quality parts and to expand the applications of additive manufacturing. Furthermore, other desirable features and characteristics of the present invention will become apparent from the subsequent detailed description of the invention and the appended claims, taken in conjunction with the accompanying drawings and this background of the invention.

BRIEF SUMMARY

(5) This summary is provided to describe select concepts in a simplified form that are further described in the Detailed Description section. This summary is not intended to identify key or essential features of the claimed subject matter, nor is it intended to be used as an aid in determining the scope of the claimed subject matter.

(6) Systems and methods are provided that resolve stresses in additive manufacturing. In a number of embodiments, a stress relief profile of an ultrasonic input is determined based on physical properties of the product. Successive layers of a material are added and energy is applied to incorporate the material of each layer into the product. An ultrasonic input is applied according to the determined parameters to resolve stresses as the product is built up. The ultrasonic input is dynamically changed as a function of material thickness along the additive build direction to

account for the changes in residual stresses due to increased thermal mass of the built-up part of the product.

(7) In a number of additional embodiments, an ultrasonic transducer is coupled with a build platform. A powder delivery system adds successive layers of a material to build the product. A laser system adds energy to incorporate the material of each layer into the product. A controller applies a signal to the ultrasonic transducer to produce an ultrasonic input having parameters to resolve stresses as the product is built up, and the ultrasonic input is dynamically changed as a function of material thickness along the additive build direction.

(8) In other embodiments, a stress relief profile with frequency and amplitude parameters of an ultrasonic input are determined based on physical properties of the product. A powder delivery system adds successive layers of a material to build the product. A laser system adds energy to incorporate the material of each layer into the product. An ultrasonic transducer applies the ultrasonic input with the determined parameters to resolve stress as the product is built up, and varies the frequency and amplitude as a depth of the material incorporated into the product increases. Additionally, the ultrasonic transducer applies an acoustic profile tailored to settle the powder layers on the built-up part thereby resulting in increased densification of the material.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The present invention will hereinafter be described in conjunction with the following drawing figures, wherein like numerals denote like elements, and wherein:

(2) FIG. 1 is a schematic illustration of a system for stress resolution in laser metal powderbed fusion, according to an exemplary embodiment;

(3) FIG. 2 is a schematic illustration of a system for stress resolution in direct energy deposition, according to an exemplary embodiment;

(4) FIG. 3 is a perspective illustration of a product for additive manufacture build, according to an exemplary embodiment;

(5) FIG. 4 is a schematic illustration of a stress resolution system in a first state of build, according to an exemplary embodiment;

(6) FIG. 5 is a diagram of a control system for controlling the stress resolution system of FIG. 4, according to an exemplary embodiment;

(7) FIG. 6 is a flow chart of a method for operation of a stress resolution system, according to an exemplary embodiment; and

(8) FIG. 7 is a schematic illustration of the stress resolution system of FIG. 4 in a second state of build, according to an exemplary embodiment.

DETAILED DESCRIPTION

(9) The following detailed description is merely exemplary in nature and is not intended to limit the invention or the application and uses of the invention. As used herein, the word “exemplary” means “serving as an example, instance, or illustration.” Thus, any embodiment described herein as “exemplary” is not necessarily to be construed as preferred or advantageous over other embodiments. All of the embodiments described herein are exemplary embodiments provided to enable persons skilled in the art to make or use the invention and not to limit the scope of the invention which is defined by the claims. Furthermore, there is no intention to be bound by any expressed or implied theory presented in the preceding technical field, background, brief summary, or the following detailed description.

(10) The various illustrative logical blocks, modules, circuits, and algorithm steps described in connection with the embodiments disclosed herein may be implemented as electronic hardware, computer software, or combinations of both. Some of the embodiments and implementations are

described above in terms of functional and/or logical block components (or modules) and various processing steps. Such block components (or modules) may be realized by any number of hardware, software, and/or firmware components configured to perform the specified functions.

(11) The various illustrative logical blocks, modules, and circuits described in connection with the embodiments disclosed herein may be implemented or performed in a controller with a general purpose processor, a digital signal processor, an application specific integrated circuit, a field programmable gate array or other programmable logic device, discrete gate or transistor logic, discrete hardware components, or any combination thereof designed to perform the functions described herein. A general-purpose processor may be a microprocessor, but in the alternative, the processor may be any conventional processor, controller, microcontroller, or state machine. A processor may also be implemented as a combination of computing devices, e.g., a combination of a digital signal processor and a microprocessor, a plurality of microprocessors, one or more microprocessors in conjunction with a digital signal processor core, or any other such configuration.

(12) The steps of a process, method or algorithm described in connection with the embodiments disclosed herein may be embodied directly in hardware, in a software module executed by a processor, or in a combination of the two. A software module may reside in any form of storage medium known in the art. An exemplary storage medium may be coupled to the processor such that the processor reads information from, and writes information to, the storage medium. In the alternative, the storage medium may be integral to the processor.

(13) In a number of embodiments described herein, systems and methods for forming a product by additive manufacturing include determining stress relief profile parameters of an ultrasonic input based on physical properties of the product. A material is deposited by additive manufacturing to build up the product. With materials such as nickel, titanium and aluminum, if not resolved, extreme stresses may accumulate during the additive manufacturing build. As a result, the item being built may crack prior to being able to submit the parts into a post-build stress relief cycle. Accordingly, ultrasonic input is applied to the deposited material to dynamically relieve stresses as the product is built up. In a number of embodiments, the ultrasonic input is varied as a material thickness along the additive build direction depth increases. In additional embodiments, in-situ measurement data may be collected to provide direct input into the ultrasonic cycle to provide customized stress relief treatment based on measurement data showing where and to what degree a part is deforming as an external indication of internal stresses. While the exemplary embodiments described herein may involve particular additive manufacturing processes, the systems and methods of the current disclosure are not limited to those specific processes and may be employed in any number of build applications where dynamic stress relief is desired.

(14) Referring to FIG. 1, a build system **20** with a stress resolution system **22** is schematically illustrated. In this embodiment, the build system **20** is a laser metal powderbed fusion system and includes a build chamber **24** that defines a sealed environment for processing. A laser system **26** is disposed within the build chamber **24** for melting a powder that is selectively deposited one layer at a time. A build platform **28** is configured for repositioning at various heights within the build chamber **24** during a build process. A build plate **30** is attached to the build platform **28** to move therewith, and to provide a surface upon which the products being built are disposed. An ultrasonic transducer **32** is coupled with the build platform **28**. Inside the build chamber **24**, powder (not shown), is spread on the surface of a build plate **30**. A laser beam from the laser system **26** is selectively directed on the deposited powder to melt or sinter the layer of powder while also anchoring it to the build plate **30**. The build platform **28** is then lowered by the depth of one layer. Additional powder is recoated over the surface, such as with a roller, blade or wiper (not shown), and the process repeated for the next layer. In a number of embodiments, the process may be paused briefly at a given layer or layers and the ultrasonic transducer **32** is activated according to a stress relief profile at an optimal frequency, power and spectrum for the given material and

machine to relieve the residual stresses from metal solidification and cooling, then the additive manufacturing operation is continued. In additional embodiments, the ultrasonic transducer **32** is activated according to a stress relief profile concurrent with operation of the laser system **26** to prevent the creation of stresses. The number of layers in various product builds vary significantly. The build layer interval between stress relief actions decreases as crack propensity increases. For purposes of the present disclosure, stress resolution means relieving stresses that have accumulated and also means avoiding stresses before they accumulate.

(15) Referring to FIG. **2**, an embodiment with a directed energy deposition system **40** with a stress resolution system **42** is schematically illustrated. The directed energy deposition system **40** involves focusing an area of intense energy into an introduced material to bond to the surrounding material. The material may be introduced through blowing, spraying, pushing or other means. In this embodiment, a directed energy deposition head **44** is attached to 5-axis movable head carrier **46**. Material is applied to the build plate **48** and melted by the directed energy deposition head **44**. The build plate **48** is attached to a 2-axis rotatable build platform **50**. An ultrasonic transducer **52** is coupled to the build plate **48**. During the directed energy deposition, material deposition may be paused briefly and the ultrasonic transducer **52** is activated according to a stress relief profile at the optimal frequency, power and spectrum for the given material and machine to relieve the residual stresses from metal solidification and cooling, then normal operation would be restarted. In additional embodiments, the ultrasonic transducer is activated during the deposition of material. This may change the grain structure of the material as the metal solidifies avoiding the creation of stresses altogether.

(16) As illustrated in FIG. **3**, an exemplary product **60** is shown as a candidate for additive manufacture using the systems and methods disclosed herein. The product **60** is a three dimensional object defined in the x direction **62**, the y direction **64**, and the z direction **66**. In this example the product **60** is a relatively simple object with a height **68** in the y direction **64**, but it will be appreciated that in various applications the geometry will be much more complex. However, even in this example the product **60** has a width **70** in the x direction **62** that varies significantly with the height **68** between segment **71** and segment **73**. Accordingly, the need to resolve stresses will be different as the width **70** varies at different heights **68**. For example, the properties of segment **71** may vary significantly from the properties of segment **73** for use in determining the applicable stress relief profile.

(17) With reference to FIG. **4**, the build system **20** is illustrated in greater detail and generally includes the stress resolution system **22**, which includes a control system **72**. The control system **72** includes a controller **74**. In other embodiments, any number of controllers may be used in place of the controller **74**. For purposes of the current embodiment, the controller **74** controls operation of the build system **20** including of a powder delivery system **80** via the actuator **78**, the laser system **26** via the actuator **76**, and the height of the build platform **28** via the actuator **82**. The controller **74** may comprise any number of electronic control modules and receive various input variables of current operating conditions and other parameters. The inputs are analyzed and operating parameters such as operation of the laser system **26**, ultrasonic transducer **32**, and others are computed from the data and applied to the actuators **76**, **78** and other responsive devices as appropriate. The controller **74** may receive various signals, including from a sensor suite **84** and a position sensor **86**, conduct analyses, and send control signals to various destinations, including to the actuators **76**, **78** and the ultrasonic transducer **32**. The actuator **78** may be a linear motor or a combination of motors or other actuators to deliver a layer of powder to the build plate **30**. The actuator **76** may be a multi-axis locator to move the laser system **26** vertically and horizontally. The actuator **82** may be a piston or motor to move the build platform **28** vertically within the cylinder **88**. The position sensor **86** senses the vertical position of the build platform **28**. The sensor suite **84** senses various aspects of the product **60** and its build including detecting its physical disposition for detecting distortion. Accordingly, the sensor suite **84** may include position sensors, optical

sensors, and other sensors as described below.

(18) The controller **74** may comprise any number of electronic control modules, including the exemplary modules described below. The controller **74** receives information from various sources, process that information, and provides control signals/commands based thereon to effect operation of the build system **20**. The controller **74** includes a processor **90** and a memory device **92**, and is coupled with a storage device **94**. The processor **90** performs the computation and control functions of the controller **74** and during operation executes one or more programs **96** and may use data **98**, each of which may be contained within the storage device **94** and as such, the processor **90** controls the general operation of the controller **74** in executing the processes described herein, such as the processes described further below. The memory device **92** may be any type of suitable memory or combination of memory devices capable of storing data, some of which represent executable instructions, used by the controller **74**. In the illustrated embodiment, the memory device **92** may store the above-referenced programs **96** along with one or more stored values of the data **98** such as for short-term data access. The storage device **94** stores data, such as for long-term data access for use in automatically controlling the build system **20** and may be any suitable type of storage apparatus. In an exemplary embodiment, the storage device **94** comprises a source from which the memory device **92** receives the programs **96** and data **98**. The programs **96** represent executable instructions, used by the controller **74** in processing information and in controlling the build system **20**, including the stress resolution system **22**. The processor **90** may generate control signals for the build system **20**, including the stress resolution system **22** based on the logic, calculations, methods, and/or algorithms.

(19) As the build progresses, powderbed **99** is deposited in individual layers on the build plate **30** and the laser system **26** selectively energizes the powder to form the product **60** according to its design parameters. The ultrasonic transducer **32** may be activated after a layer is fused into the product **60** or while the fusing is taking place. The layers for which the ultrasonic transducer **32** is activated may be predefined and stored in memory and may be recalled according to the location of the build platform **28** as sensed by the position sensor **86**. In other embodiments, the sensor suite **84** may be monitored to determine whether distortion or other aspects of the product **60** indicate activation of the ultrasonic transducer **32** is needed to provide stress resolution.

(20) As illustrated in FIG. 5, the control system **72** may include a number of modules to operate the build system **20**, including the stress resolution system **22**. In embodiments, the control system **72** generally includes a stress resolution module **102**, an actuator control module **104**, an ultrasonic operation module **106**, and a datastore **108**. The control system **72** may include any number of additional modules to control aspects of the build system **20** independent of, or in coordination with, the modules shown in FIG. 5. Inputs may include a signal **110** from the sensor suite **84** and a signal **112** from the position sensor **86**. Outputs may include a signal **116** to operate the actuator **76** of the laser system **26**, a signal **118** to operate the actuator **78** of the powder delivery system **80**, a signal **120** to operate the actuator **82** of the build platform **28**, and a signal **122** to operate the ultrasonic transducer **32**. In general, when a determination is made to operate the ultrasonic transducer **32** to resolve stresses, the ultrasonic operation module **106**, delivers the signal **122** to the ultrasonic transducer **32** to impart energy through the build platform **28** and the build plate **30** to the in-process product **60** to relieve or avoid stresses therein.

(21) Referring additionally to FIG. 6, a process **200** to resolve stresses begins **202** with the geometry and physical properties of the exemplary product **60** being determined **204** according to design requirements. For example, the physical dimensions of the product **60** are determined **204** and the material from which the product **60** will be made is determined **204**. Given the geometry, predeterminations **206**, **208** may be made by analysis such as based on calculations and/or testing. More specifically, resonant frequencies of the product **60** may be determined **206** for the product **60** as partially built through various build layer stages. The resonant frequencies of the product **60** may be calculated and vary as the height of the build progresses. In a simple example of printing a

straight, vertical rectangular bar such as the segment **73** of the product **60**, as the build progresses the resonant frequency of the segment will decrease as it becomes higher. In a build with multiple parts or segments with complex geometries, as the build progresses the resonant properties of the system will change throughout the build. For example, the resonant frequencies between the segments **71** and **73** will differ substantially. Resonant frequencies for given build configurations (at specific build layers, or cross sections) may be determined with analytical software or by using the results of machine-learning data from prior builds. Once determined **206**, the resonance data may be stored, such as in the datastore **108**.

(22) A stress relief profile, including stress relief frequencies and power levels may be determined **208**, such as in advance based on modeling, experimentation and/or testing of the product **60**. The process **200** proceeds to build **210** a layer of the product **60**, such as by operation of the actuators **76**, **78** via the actuator control module **104** to deposit material and incorporate the layer into the product **60**. Where predetermined for a given product **60**, the stress relief frequencies and power levels may be stored, such as in the datastore **108** for given build layers. The frequency and power level of the energy supplied by the ultrasonic transducer **32** is tailored to the physical properties of the product **60**, including the material used for fabrication, and varies by build level. For example, as shown in FIG. **4**, as the segment **71** is being built, the properties will be different than those as the segment **73** is being built as shown in FIG. **7**. In the current embodiment, the stress resolution module **102** may determine the frequency and power levels based on data retrieved from the datastore **108**. The ultrasonic transducer **32** is activated according to the stress relief profile at the optimal frequency, power and spectrum for the given material and machine to relieve the residual stresses, such as may arise from metal solidification and cooling.

(23) In a number of embodiments, the stress relief profile including power and frequency for the ultrasonic excitation may be determined **214**, such as by the stress resolution module **102**, based on inputs obtained during the build that are read **212**, such as from the sensors **84**, **86**. The sensor **86** provides feedback on the build layer of the product **60** and the sensor suite **84** provides information on the product **60**, including where a deviation from the design dimensions may be actual or incipient. Sensing distortion enables targeting ultrasonic inputs to individual layers where stress resolution is needed based on the actual build underway. In addition, the collected data may be stored **216** and/or transmitted. For example, an industrial internet of things application may transmit in-situ measurement data to provide direct input of the ultrasonic cycle to provide customized stress relief treatment based on measurement data showing where and to what degree a part is deforming as an external indication of internal stresses.

(24) In embodiments, automated adjustments are made to the stress relief profile and stored, such as for use in the determination **208**, when distortion or other parameters measured exceed set limits. Anticipated build process monitors in the sensor suite **84** may include melt pool sensors, thermal sensors, optical distortion sensors, build plate strain gauges, and others. Data from the sensors is aggregated and implemented into system software that learns as the system matures and incorporates feedback from other connected systems. In a number of embodiments, by iteratively processing build data against stress resolution inputs and other build parameters, the ultrasonic stress resolution may be used to automatically determine an optimal stress relief profile for a new part (or mix of parts) to be printed.

(25) With the stress relief profile determined **208**, **214**, an evaluation **220** is made to verify whether ultrasonic stress resolution is needed for the product **60** at the stage of the newly built layer. For example, when the determination **208** is based on a predetermined and stored data, the evaluation **220** outcome is positive when the layer built coincides with one targeted for stress resolution. Also, for example, when the determination **214** concludes that deformation is incipient or started, the evaluation **220** outcome is positive when the layer just built requires stress resolution to correct deformation. When neither is found, the evaluation **220** outcome is negative, and the process **200** returns to build **210** another layer such as by depositing powder by the powder delivery system **80**

and activation of the laser system **26**.

(26) Following a positive determination **220**, the process **200** continues with an evaluation **222** as to whether there is overlap between resonant frequencies of the product **60** in its current configuration and the determined **208, 214** frequency. Effectively resolving the stresses in the additive manufactured product **60** includes adapting the frequencies of the ultrasonic input to optimize for the changing harmonic characteristics of a part. This involves exciting at certain frequencies, while excluding other frequencies to be able to both relieve the stresses built up within the build and to avoid damaging vibrations due to hitting certain resonant frequencies. When the outcome of the evaluation **222** is negative, and there is no overlap between the determined frequency and the resonant frequency, the process **200** proceeds to operate **224**, the ultrasonic transducer **32** according to the stress relief profile. When the evaluation **222** is positive, meaning there is overlap between the resonant frequency and the determined **208/214** frequency, the process **200** reconciles **223** the overlap. For example, the frequency delivered by the ultrasonic transducer **32** may be revised to fall outside the resonant frequency range to avoid damaging resonant vibrations. The result is to tune each exposure of ultrasonic cycles throughout the build to selectively excite the system to resolve the stresses while avoiding resonant frequencies.

(27) With the frequency and power of the ultrasonic input determined **208, 214** and the need for stress resolution verified **220**, along with any reconciliation **223**, the process **200** proceeds to operate **224** the ultrasonic transducer **32**, such as by the signal **122** from the ultrasonic operation module **106**. The build system **20** is widely capable of efficiently adjusting both frequency content and amplitude to adjust to the resonant characteristics of a wide range of build profiles containing any combination of parts to be manufactured. A high-power, tunable build system **20** enables delivering the stress resolution energy input through the single ultrasonic transducer **32**. When the process **200** determines **226** that the product **60** is complete, the process ends **228**. When the determination **226** is negative, the process **200** returns to build **210** an additional layer.

(28) In embodiments with metal powderbed style additive manufacturing, a cover **95** (FIG. 7), such as a plate or sheet that covers the metal powderbed during the ultrasonic exposure period may be used to prevent scatter of metal powder out from the build area. Operation of the laser system **26** is suspended when the cover **95** is deployed. The cover **95** may be any variation of a sheet, film or plate, and may be pulled by the powder delivery system **80** over the powderbed **99**. In other embodiments, the cover **95** may be a sheet, film or plate that is lowered or slid over the powderbed **99**. In some embodiments, following step **224**, the stress resolution treatment, the ultrasonic transducer **32** is separately activated to produce a different acoustic profile tailored to settle and compact the metal powderbed **99**.

(29) Through the examples described herein, stress resolution is effected during the additive manufacture of items. Resolving stress while a product is being made improves quality part yield and reduces costs. In addition, part distortion is mitigated or eliminated from occurring. Using ultrasonic energy driven into the components through the build platform, relieves the stresses accumulating in the build and may be addressed before reaching a point of either inducing distortion or ultimately cracking. The ultrasonic stress resolution system is compact, low-cost, energy efficient and has a relatively small footprint. Advantageously, parts may be manufactured with significantly higher speeds and yields for reduced costs and at shorter lead-times.

Additionally, the systems and methods disclosed herein enable fabricating components from materials and with geometries that otherwise would not be viable using additive manufacturing.

(30) While at least one exemplary embodiment has been presented in the foregoing detailed description, it should be appreciated that a vast number of variations exist. It should also be appreciated that the exemplary embodiment or exemplary embodiments are only examples, and are not intended to limit the scope, applicability, or configuration of the invention in any way. Rather, the foregoing detailed description will provide those skilled in the art with a convenient road map for implementing an exemplary embodiment of the invention. It being understood that various

changes may be made in the function and arrangement of elements described in an exemplary embodiment without departing from the scope of the invention as set forth in the appended claims.

Claims

1. A system for stress relief in forming a product by additive manufacturing, the system comprising: a build surface; a stress relief system including a transducer coupled with the build surface, the transducer configured to generate a frequency and a power so the stress relief system is configured to deliver stress relief energy to the build surface; a material delivery system configured to add successive layers of a material to build the product on the build surface; an energy system configured to add build energy to incorporate the material of each of the successive layers into the product; and at least one controller configured to: coordinate operation of the stress relief system, the material delivery system and the energy system to complete the build of the product; determine stress relief parameters throughout the build of the product, where the stress relief parameters include frequency and amplitude parameters and are at least one of predetermined or based on input from at least one sensor; determine, by a processor of the at least one controller and based on the stress relief parameters, where, during the build of the product, stress relief is required based on where a deviation from design parameters of the product is indicated as incipient or actual; and apply, by the transducer of the stress relief system and when the processor has determined that the stress relief is required, an input to the stress relief system with a power level tailored to relieve stress according to the stress relief parameters as determined by the at least one controller.
2. The system of claim 1, wherein the transducer comprises an ultrasonic transducer, wherein the at least one controller is configured to deliver, via the ultrasonic transducer of the stress relief system, a customized stress relief treatment of the product based on measurement data from the at least one sensor showing where and to what degree the product is deforming, or is about to deform, as an external indication of internal stresses.
3. The system of claim 1, wherein the at least one controller is configured to define and to optimize the build of the product, and is configured to make automated adjustments to the stress relief parameters when distortion measured by the at least one sensor exceeds set limits.
4. The system of claim 1, wherein the at least one controller is configured to determine whether there is overlap between resonant frequencies of the product in its current configuration and the frequency of the stress relief parameters and to avoid the resonant frequencies.
5. The system of claim 1, wherein the at least one controller is configured to automatically generate the stress relief parameters for a new product, and is configured to aggregate data from the at least one sensor and iteratively process the data against the stress relief parameters and other parameters of a new part to be printed to automatically determine an optimal stress relief parameter set for the new part.
6. The system of claim 1, wherein the stress relief parameters are based on input from the at least one sensor and the design parameters comprise design dimensions of the product.
7. The system of claim 1, wherein the stress relief parameters are defined by a profile, wherein the at least one controller is configured to access the profile for each individual layer of the successive layers, and to apply the input only when the profile indicates the deviation from design parameters exists.
8. The system of claim 1, wherein the build surface is configured to support a powder bed and comprising a cover configured to cover the powder bed during the apply of the input by the stress relief system.
9. The system of claim 1, wherein the transducer comprises an ultrasonic transducer, configured to apply the input to the stress relief system.
10. The system of claim 1, wherein the at least one controller comprises a plural number of controllers configured to: collect data from the at least one sensor; transmit the data; create

customized stress relief treatments based on the data to automatically determine optimal stress relief parameters; and effect, through the stress relief system, the stress relief of internal stresses during the build of the product.

11. A system for stress relief in forming a product by additive manufacturing, the system comprising: a build surface; a stress relief system including an ultrasonic transducer coupled with the build surface, the stress relief system configured to deliver stress relief energy to the build surface; a material delivery system configured to add successive layers of a material to build the product on the build surface; an energy system configured to add build energy to incorporate the material of each of the successive layers into the product; and at least one controller configured to: coordinate operation of the stress relief system, the material delivery system and the energy system to complete the build of the product; determine stress relief parameters throughout the build of the product to define a profile, where the stress relief parameters include frequency and amplitude parameters and are at least one of predetermined or based on input from at least one sensor; determine, by a processor of the at least one controller and based on the stress relief parameters, where, during the build of the product, stress relief is required based on where a deviation from design parameters of the product is indicated as incipient or actual; and apply, by the ultrasonic transducer of the stress relief system and only when the at least one controller has determined that the stress relief is required, an input to the stress relief system with a power level according to the profile that is tailored to relieve stress according to the stress relief parameters as determined by the at least one controller.
