

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412867
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Wang; Jhih-Yu et al.

Integrated fan-out package and manufacturing method thereof

Abstract

An integrated fan-out (InFO) package includes a die, an encapsulant laterally encapsulating the die, and a redistribution structure. The redistribution structure is disposed on the encapsulant. The redistribution structure includes a plurality of routing patterns and a plurality of alignment marks. The routing patterns are electrically connected to the die. The alignment marks surround the routing patterns. The alignment marks are electrically insulated from the die and the routing patterns. At least one of the alignment marks is in physical contact with the encapsulant, and the alignment marks located at different level heights are arranged in a non-overlapping manner vertically.

Inventors: Wang; Jhih-Yu (New Taipei, TW), Kuo; Hung-Jui (Hsinchu, TW), Hu; Yu-Hsiang (Hsinchu, TW), Liao; Sih-Hao (New Taipei, TW), Chu; Yung-Chi (Kaohsiung, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 68840709

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 18/396575

Filed: December 26, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240186283 A1	Jun. 06, 2024

Related U.S. Application Data

continuation parent-doc US 17465872 20210903 US 11894336 child-doc US 18396575
continuation parent-doc US 16009211 20180615 US 11114407 20210907 child-doc US 17465872

Publication Classification

Int. Cl.: H01L23/00 (20060101); H01L23/544 (20060101); H01L25/065 (20230101)

U.S. Cl.:

CPC H01L24/82 (20130101); H01L23/544 (20130101); H01L24/02 (20130101); H01L24/24 (20130101); H01L24/25 (20130101); H01L25/0655 (20130101); H01L2223/54426 (20130101); H01L2223/54486 (20130101); H01L2224/02313 (20130101); H01L2224/02331 (20130101); H01L2224/02379 (20130101); H01L2224/02381 (20130101); H01L2224/24011 (20130101); H01L2224/24137 (20130101); H01L2224/24155 (20130101); H01L2224/25171 (20130101); H01L2224/82106 (20130101); H01L2224/82132 (20130101)

Field of Classification Search

CPC: H01L (24/82); H01L (23/544); H01L (23/3128); H01L (23/3114); H01L (23/522); H01L (23/5226); H01L (24/02); H01L (24/20); H01L (24/24); H01L (24/25); H01L (24/0655); H01L (2223/54426); H01L (2223/54486); H01L (2223/02379); H01L (2224/02313); H01L (2224/02331); H01L (2224/02381); H01L (2224/24011); H01L (2224/24137); H01L (2224/24155); H01L (2224/25171); H01L (2224/82106); H01L (2224/82132); H01L (2224/04105); H01L (2224/32145); H01L (2224/32225); H01L (2224/48227); H01L (2224/73265); H01L (2224/12105); H01L (2224/73267); H01L (2224/92244); H01L (2224/96); H01L (25/0657); H01L (25/105); H01L (2221/68345); H01L (2221/68359); H01L (2225/0651); H01L (2225/06568); H01L (2924/15311); H01L (21/561); H01L (21/6835); H01L (21/4814); H01L (2924/00012); H01L (2924/00)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
11114407	12/2020	Wang	N/A	H01L 24/24
11894336	12/2023	Wang	N/A	H01L 24/20

Primary Examiner: Page; Dale E

Assistant Examiner: Jefferson; Quovaunda

Attorney, Agent or Firm: JCIPRNET

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a continuation application of and claims the priority benefit of a prior application Ser. No. 17/465,872, filed on Sep. 3, 2021. The prior application Ser. No. 17/465,872 is a continuation application of and claims the priority benefit of a prior application Ser. No. 16/009,211, filed on Jun. 15, 2018. The entirety of each of the above-mentioned patent applications is hereby incorporated by reference herein and made a part of this specification.

BACKGROUND

(1) The semiconductor industry has experienced rapid growth due to continuous improvements in the integration density of various electronic components (e.g., transistors, diodes, resistors, capacitors, etc.). For the most part, this improvement in integration density has come from repeated reductions in minimum feature size, which allows more of the smaller components to be integrated into a given area. These smaller electronic components also require smaller packages that utilize less area than previous packages. Currently, integrated fan-out packages are becoming increasingly popular for their compactness. However, there are many challenges related to integrated fan-out packages.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1A to FIG. 1Y are schematic cross-sectional views illustrating a manufacturing process of an integrated fan-out (InFO) package in accordance with some embodiments of the disclosure.

(3) FIG. 2A to FIG. 2C are schematic top views illustrating various configurations of the first alignment mark in FIG. 1H.

(4) FIG. 3A to FIG. 3B are schematic cross-sectional views illustrating an intermediate stage of a manufacturing process of an InFO package in accordance with some alternative embodiments of the disclosure.

(5) FIG. 4 is a schematic cross-sectional view illustrating a package-on-package (PoP) structure.

(6) FIG. 5 is a cross-sectional view illustrating an InFO package in accordance with some alternative embodiments of the disclosure.

(7) FIG. 6A to FIG. 6I are schematic cross-sectional views illustrating intermediate stages of a manufacturing process of an InFO package in accordance with some alternative embodiments of the disclosure.

DETAILED DESCRIPTION

(8) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(9) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(10) Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

(11) FIG. 1A to FIG. 1Y are schematic cross-sectional views illustrating a manufacturing process of an integrated fan-out (InFO) package **10** in accordance with some embodiments of the disclosure. Referring to FIG. 1A, a carrier **C** having a de-bonding layer **DB** formed thereon is provided. In some embodiments, the carrier **C** is a glass substrate. However, other material may be adapted as a material of the carrier **C** as long as the material is able to withstand the following manufacturing processes while supporting the elements formed thereon. In some embodiments, the de-bonding layer **DB** is a light-to-heat conversion (LTHC) release layer formed on the glass substrate. The de-bonding layer **DB** allows the structure formed on the carrier **C** in the subsequent processes to be peeled off from the carrier **C**.

(12) A redistribution structure **100** is formed over the carrier **C**. In some embodiments, the redistribution structure **100** is attached to the de-bonding layer **DB**. In some embodiments, the redistribution structure **100** includes a dielectric layer **104**, a redistribution conductive layer **102**, and a plurality of redistribution conductive vias **106**. The redistribution conductive layer **102** may be constituted by a plurality of redistribution conductive patterns. For simplicity, the dielectric layer **104** is illustrated as one single layer of dielectric layer and the redistribution conductive layer **102** is illustrated as embedded in the dielectric layer **104** in FIG. 1A. Nevertheless, from the perspective of the manufacturing process, the dielectric layer **104** is constituted by two dielectric layers and the redistribution conductive layer **102** is sandwiched between the two adjacent dielectric layers. As illustrated in FIG. 1A, the redistribution conductive vias **106** are also embedded in the dielectric layer **104**. In some embodiments, materials of the redistribution conductive layer **102** and the redistribution conductive vias **106** include aluminum, titanium, copper, nickel, tungsten, and/or alloys thereof. The redistribution conductive layer **102** may be formed by, for example, electroplating, deposition, and/or photolithography and etching. In some embodiments, the material of the dielectric layer **104** includes polyimide, epoxy resin, acrylic resin, phenol resin, benzocyclobutene (BCB), polybenzooxazole (PBO), or any other suitable polymer-based dielectric material. The dielectric layer **104**, for example, may be formed by suitable fabrication techniques such as spin-on coating, chemical vapor deposition (CVD), plasma-enhanced chemical vapor deposition (PECVD), or the like.

(13) It should be noted that the number of the redistribution conductive layers **102** and the number of the dielectric layers **104** illustrated in FIG. 1A are merely for illustrative purposes, and the disclosure is not limited thereto. In some alternative embodiments, more layers of the redistribution conductive layer and more layers of the dielectric layer may be formed depending on the circuit design. When more layers of redistribution conductive layer and more layers of the dielectric layer are adapted, these redistribution conductive layers and these dielectric layers are stacked alternately, and the redistribution conductive layers are interconnected with one another by the redistribution conductive vias. In some embodiments, the redistribution structure **100** is referred to as a back-side redistribution structure.

(14) A plurality of conductive structures **200** are formed on the redistribution structure **100**. In some embodiments, the InFO package **10** has an active region **AR** and a border region **BR** surrounding the active region **AR**. The conductive structures **200** may be formed, for example, in the active region **AR**. In some embodiments, the conductive structures **200** are conductive pillars formed by a photolithography process, a plating process, a photoresist stripping processes, and/or

any other suitable processes. In some embodiments, the conductive structures **200** are formed on the redistribution conductive vias **106** and are in contact with the redistribution conductive vias **106** to render electrical connection with the redistribution structure **100**. In some embodiments, the conductive structures **200** may be formed simultaneously with the redistribution conductive vias **106** during the same stage. For example, a plurality of contact openings corresponding to the designated location of the redistribution conductive vias **106** may be formed in the dielectric layer **104**. Subsequently, a seed material layer (not shown) extending into the contact openings may be formed over the dielectric layer. A mask pattern (not shown) may then be formed on the seed material layer. The mask pattern has openings exposing the seed material layer located inside of the contact openings. In some embodiments, the openings of the mask pattern also exposes portions of the seed material layer in proximity of the contact openings. Thereafter, a conductive material is filled into the openings and the contact openings by electroplating or deposition. Then, the mask pattern and the seed layer underneath the mask pattern is removed to obtain the conductive structures **200** and the redistribution conductive vias **106**. However, the disclosure is not limited thereto. Other suitable methods may be utilized to form the conductive structures **102** and the redistribution conductive vias **106**. For example, the conductive structures **200** and the redistribution conductive vias **106** may be formed separately. In some alternative embodiments, a plurality of conductive pads (not shown) may be formed over the redistribution conductive vias **106**. The conductive structures **200** are formed over the conductive pads such that the conductive structures **200** are electrically connected to the redistribution structure **100** through the conductive pads.

(15) In some embodiments, a material of the conductive structures **200** includes copper, copper alloys, or the like. It should be noted that the number of the conductive structures **200** shown in FIG. **1A** merely serves as an exemplary illustration, and the number of the conductive structures **200** may be varied based on demand.

(16) Referring to FIG. **1B**, a plurality of dies **300** are formed on the redistribution structure **100**. In some embodiments, the dies **300** are placed between the conductive structures **200** in the active region AR. For example, the conductive structures **200** may be arranged to surround the dies **300**. In some embodiments, the dies **300** are picked and placed onto the redistribution structure **100**. Each of the dies **300**, for example, includes a semiconductor substrate **310**, a plurality of conductive pads **320**, a passivation layer **330**, a post passivation layer **340**, a plurality of vias **350**, and a protection layer **360**. In some embodiments, the conductive pads **320** are disposed over the semiconductor substrate **310**. The passivation layer **330** is formed over the semiconductor substrate **310** and has contact openings that partially expose the conductive pads **320**. The semiconductor substrate **310** may be a silicon substrate including active components (e.g., transistors or the like) and passive components (e.g., resistors, capacitors, inductors, or the like) formed therein. The conductive pads **320** may be aluminum pads, copper pads, or other suitable metal pads. The passivation layer **330** may be a silicon oxide layer, a silicon nitride layer, a silicon oxy-nitride layer, or a dielectric layer formed by other suitable dielectric materials. Furthermore, the post-passivation layer **340** is formed over the passivation layer **330**. The post-passivation layer **340** covers the passivation layer **330** and has a plurality of contact openings. The conductive pads **320** are partially exposed from the contact openings of the post passivation layer **340**. The post-passivation layer **340** may be a polyimide (PI) layer, a PBO layer, or a dielectric layer formed by other suitable polymers. In some embodiments, the post-passivation layer **340** may be optional. In addition, the vias **350** are formed on the conductive pads **320**. In some embodiments, the vias **350** are made of conductive materials and are plated on the conductive pads **320**. The protection layer **360** is formed on the post-passivation layer **340** to cover the vias **350**.

(17) As illustrated in FIG. **1B**, each die **300** has a rear surface **300a** and a front surface **300b** opposite to the rear surface **300a**. In some embodiments, the rear surfaces **300a** of the dies **300** are attached (or adhered) to the redistribution structure **100** through an adhesive layer AD. In some

embodiments, the adhesive layer AD may include a die attach film (DAF). On the other hand, the front surfaces **300b** of the dies **300** face upward. As illustrated in FIG. **1B**, top surfaces (front surface **300b**) of the dies **300** are substantially coplanar with top surfaces of the conductive structures **200**. However, the disclosure is not limited thereto. In some alternative embodiments, the top surfaces of the dies **300** may be located at a level height lower than or higher than the top surfaces of the conductive structures **200**. Although two dies **300** are shown in FIG. **1B**, the configuration merely serves as an exemplary illustration. In some alternative embodiments, more or less number of dies may be formed based on demand.

(18) Referring to FIG. **1C**, an encapsulation material **400a** is formed over the redistribution structure **100** to encapsulate the conductive structures **200** and the dies **300**. For example, the conductive structures **200** and the protection layer **360** of the dies **300** are encapsulated by the encapsulation material **400a**. In other words, the conductive structures **200** and the protection layer **360** of the dies **300** are not revealed and are well protected by the encapsulation material **400a**. In some embodiments, the encapsulation material **400a** is a molding compound, a molding underfill, a resin (such as epoxy), or the like. The encapsulation material **400a** may be formed by a molding process. For example, the encapsulation material **400a** may be formed by a compression molding process.

(19) Referring to FIG. **1C** and FIG. **1D**, the encapsulation material **400a** and the protection layer **360** of the dies **300** are grinded until top surfaces of the vias **350** are exposed. After the encapsulation material **400a** is grinded, an encapsulant **400** is formed over the redistribution structure **100** to encapsulate the conductive structures **200** and the dies **300**. In some embodiments, the encapsulant material **400a** is grinded by a mechanical grinding process and/or a chemical mechanical polishing (CMP) process. In some embodiments, during the grinding process of the encapsulant material **400a**, the protection layer **360** is grinded to reveal the vias **350**. In some embodiments, portions of the vias **350** and portions of the conductive structures **200** are slightly grinded as well. After grinding, each die **300** has an active surface **300c** and a rear surface **300a** opposite to the active surface **300c**. The exposed portion of the vias **350** is located on the active surfaces **300c** of the dies **300**. It is noted that the top surfaces of the conductive structures **200**, the top surface of the protection layer **360**, and the top surfaces of the vias **350** are substantially coplanar with a top surface of the encapsulant **400**.

(20) Referring to FIG. **1E**, a seed material layer **510** is formed on the encapsulant **400**, the conductive structures **200**, and the die **300**. In some embodiments, the seed material layer **510** is blanketly formed over the encapsulant **400**, the conductive structures **200**, and the die **300**. For example, the seed material layer **510** is formed to locate in both of the active region AR and the border region BR. In some embodiments, the seed material layer **510** is formed to be in direct contact with the conductive structures **200**, the encapsulant **400**, the protection layer **360**, and the vias **350**. The seed material layer **510** may be formed through, for example, a sputtering process, a physical vapor deposition (PVD) process, or the like. In some embodiments, the seed material layer **510** may include, for example, copper, titanium-copper alloy, or other suitable choice of materials.

(21) Referring to FIG. **1F**, a photoresist layer PR1 is formed over the seed material layer **510**. In some embodiments, the photoresist layer PR1 may be formed through spin-coating or other suitable formation methods. As illustrated in FIG. **1F**, the photoresist layer PR1 has a plurality of openings OP1 exposing at least a portion of the seed material layer **510**. In some embodiments, two adjacent openings OP1 in the border region BR may be closer than two adjacent openings OP1 in the active region AR. For example, a distance between two adjacent openings OP1 in the border region BR may be smaller than a distance between two adjacent openings OP1 in the active region AR. In some embodiments, some of the openings OP1 in the active region AR correspond to the locations of the conductive structures **200** and the vias **350**. For example, a vertical projection of some of the openings OP1 along a direction perpendicular to the active surface **300c** of the dies **300** overlaps with the conductive structure **200**. Similarly, a vertical projection of some of the openings

OP1 along the direction perpendicular to the active surface 300c of the dies 300 overlaps with the vias 350 of the dies 300.

(22) Referring to FIG. 1F and FIG. 1G, a plurality of conductive patterns 520a, 520b are formed on the seed material layer 510. In some embodiments, a conductive material (not shown) is filled into the openings OP1 of the photoresist layer PR1. Thereafter, the photoresist layer PR1 is removed to obtain the conductive patterns 520a, 520b. Upon removal of the photoresist layer PR1, portions of the seed material layer 510, which are not covered by the conductive patterns 520a, 520b, are exposed. In some embodiments, the conductive material may be formed by a plating process. The plating process is, for example, electro-plating, electroless-plating, immersion plating, or the like. In some embodiments, the conductive material includes, for example, copper, copper alloys, or the like. The photoresist pattern layer PR1 may be removed/stripped through, for example, etching, ashing, or other suitable removal processes. In some embodiments, the conductive patterns 520a are located in the active region AR and the conductive patterns 520b are located in the border region BR.

(23) Referring to FIG. 1G and FIG. 1H, the seed material layer 510 that is not covered by the conductive patterns 520a, 520b is removed to render seed layers 510a, 510b. That is, the seed material layer 510 underneath the photoresist layer PR1 is removed. The exposed portions of the seed material layer 510 may be removed through an etching process. In some embodiments, the material of the conductive patterns 520a, 520b may be different from the material of the seed material layer 510, so the exposed portion of the seed material layer 510 may be removed through selective etching. The seed layer 510a is located in the active region AR and the seed layer 510b is located in the border region BR. In some embodiments, a portion of the seed layer 510a is sandwiched between the conductive structures 200 and the conductive patterns 520a and another portion of the seed layer 510a is sandwiched between the vias 350 and the conductive patterns 520a. On the other hand, the seed layer 510b is sandwiched between the encapsulant 400 and the conductive patterns 520b. In some embodiments, the conductive patterns 520a are stacked on the seed layer 510a, and the conductive patterns 520b are stacked on the seed layer 510b. In some embodiments, the seed layer 510b may include a plurality of seed layer patterns. As illustrated in FIG. 1H, the seed layer patterns are aligned with the conductive patterns 520b along a direction perpendicular to the active surface 300c of the die 300. For example, sidewalls of each seed layer pattern are aligned with sidewalls of each conductive pattern 520b.

(24) In some embodiments, the conductive patterns 520a and the seed layer 510a located in the active region AR are collectively referred to as first conductive vias CV1. On the other hand, the conductive patterns 520b and the seed layer 510b located in the border region BR may be collectively referred to as first alignment marks AM1. In some embodiments, the first conductive vias CV1 are located in the active region AR and the first alignment marks AM1 are located in the border region BR. The first conductive vias CV1 may electrically connect the conductive structures 200 and/or the vias 350 of the die 300 with other subsequently formed elements. On the other hand, the first alignment marks AM1 may ensure other subsequently formed elements are precisely formed on the designated location. In some embodiments, the first alignment marks AM1 are electrically floating. For example, the first alignment marks AM1 are electrically insulated from the first conductive vias CV1, the conductive structures 200, the vias 350 of the dies 300, and the redistribution structure 100. In some embodiments, the first alignment marks AM1 are in physical contact with the encapsulant 400. For example, the seed layer 510b of the first alignment marks AM1 may be directly in contact with the encapsulant 400.

(25) As mentioned above, the distance between two adjacent openings OP1 of the photoresist layer PR1 in the border region BR may be smaller than the distance between two adjacent openings OP1 of the photoresist layer PR1 in the active region AR. Since the first conductive vias CV1 and the first alignment marks AM1 are formed by filling the conductive material into the openings OP1, the first conductive vias CV1 and the first alignment marks AM1 may have shapes corresponding

to the contour of the openings OP1. For example, each of the first conductive vias CV1 may be a bulk pattern from a top view while each of the first alignment marks AM1 may be a grid pattern from a top view. That is, one first conductive via CV1 includes one conductive pattern 520a while one first alignment mark AM1 includes multiple conductive patterns 520b. The configuration of the first alignment mark AM1 will be discussed below in conjunction with FIG. 2A to FIG. 2C.

(26) FIG. 2A to FIG. 2C are schematic top views illustrating various configurations of the first alignment mark in FIG. 1H. Referring to FIG. 2A, the conductive patterns 520b are arranged parallel to each other. Moreover, the conductive patterns 520b are separated from each other. That is, the conductive patterns 520b are arranged to form an L-shaped grid pattern. In some embodiments, the first alignment mark AM1 has a dimension of 1 μm to m. Herein, the dimension refers to the length or the width of the first alignment mark AM1 from the top view. By adapting the first alignment mark AM1 with the grid pattern, the signal noise on the first alignment mark AM1 may be sufficiently reduced. That is, the machinery is able to precisely detect the first alignment mark AM1, thereby enhancing the overlay accuracy and reducing the alignment failure rate. For example, in some embodiments, an overlay accuracy within 0.5 μm may be achieved through the adaption of the grid pattern.

(27) In some alternative embodiments, the first alignment mark AM1 may have other shapes from the top view. For example, referring to FIG. 2B, the conductive patterns 520b form a square-shaped grid pattern. The square-shaped grid pattern has an L-shaped hollow portion therein. In some embodiments, the machinery may detect the contour of the L-shaped hollow portion based on the conductive patterns 520b for alignment. FIG. 2A and FIG. 2B illustrated that all of the conductive patterns 520b in the first alignment mark AM1 are separated from each other, but the disclosure is not limited thereto. In some alternative embodiments, at least a portion of the conductive patterns 520b may be in contact with each other. For example, referring to FIG. 2C, a portion of the conductive patterns 520b are connected to each other to form a first L-shaped pattern. On the other hand, another portion of the conductive patterns 520b are connected to each other to form a second L-shaped pattern encircling the first L-shaped pattern. The conductive patterns 520b in the first L-shaped pattern are separated from the conductive patterns 520b in the second L-shaped pattern. Since at least part of the conductive patterns 520b are separated from each other, the configuration shown in FIG. 2C may also be considered as a grid pattern in some embodiments. By adapting the first alignment mark AM1 with the grid pattern, the signal noise on the first alignment mark AM1 may be sufficiently reduced and the overlay accuracy may be sufficiently enhanced.

(28) It should be noted that the configurations of the first alignment mark AM1 shown in FIG. 2A to FIG. 2C merely serve as exemplary illustrations, and the disclosure is not limited thereto. The first alignment mark AM1 may also have other shapes or take other forms as long as the first alignment mark AM1 includes a grid pattern.

(29) Referring to FIG. 1I, a dielectric material layer 530a is formed over the encapsulant 400, the conductive structures 200, and the dies 300 to encapsulate the first conductive vias CV1 and the first alignment marks AM1. In other words, the first conductive vias CV1 and the first alignment marks AM1 are not revealed and are well protected by the dielectric material layer 530a. In some embodiments, a material of the dielectric material layer 530a includes polyimide, epoxy resin, acrylic resin, phenol resin, BCB, PBO, or any other suitable polymer-based dielectric material. The dielectric material layer 530a may be formed by suitable fabrication techniques, such as spin-on coating, chemical vapor deposition (CVD), plasma-enhanced chemical vapor deposition (PECVD), or the like.

(30) Referring to FIG. 1I and FIG. 1J, a portion of the dielectric material layer 530a is removed to form a first dielectric layer 530 exposing top surfaces T.sub.CV1 of the first conductive vias CV1 and top surfaces T.sub.AM1 of the first alignment marks AM1. For example, the dielectric material layer 530a may be grinded until top surfaces T.sub.CV1 of the first conductive vias CV1 and top surfaces T.sub.AM1 of the first alignment marks AM1 are exposed. In some embodiments, the

dielectric material layer **530a** is grinded by a chemical mechanical polishing (CMP) process.

(31) In some embodiments, the dielectric material layer **530a** is grinded such that a top surface T.sub.530 of the first dielectric layer **530** is substantially coplanar with the top surfaces T.sub.CV1 of the first conductive vias **CV1** and the top surfaces T.sub.AM1 of the first alignment marks **AM1**. For example, the top surfaces T.sub.CV1 of the first conductive vias **CV1** are substantially coplanar with top surfaces of the conductive patterns **520b** of the first alignment mark **AM1**. In some embodiments, the first dielectric layer **530**, the first conductive vias **CV1**, and the first alignment marks **AM1** may have substantially the same thickness of 2 μm to 10 μm . In some alternative embodiments, due to grinding selectivity between different materials, a height difference may be seen between the top surface T.sub.530 of the first dielectric layer **530** and the top surfaces T.sub.CV1 of the first conductive vias **CV1** and between the top surface T.sub.530 of the first dielectric layer **530** and the top surfaces T.sub.AM1 of the first alignment marks **AM1**. The height differences will be described below in conjunction with FIG. 3A and FIG. 3B.

(32) FIG. 3A to FIG. 3B are schematic cross-sectional views illustrating an intermediate stage of a manufacturing process of an InFO package **10** in accordance with some alternative embodiments of the disclosure. Referring to FIG. 3A, in some embodiments, the conductive vias **CV1** and the first alignment marks **AM1** are over-grinded during the grinding process such that the top surface T.sub.530 of the first dielectric layer **530** is located at a level height higher than the top surfaces T.sub.CV1 of the first conductive vias **CV1** and the top surfaces T.sub.AM1 of the first alignment marks **AM1**. For example, a thickness of the first conductive vias **CV1** may be smaller than a thickness of the first dielectric layer **530**. Similarly, a thickness of the first alignment mark **AM1** may also be smaller than the thickness of the first dielectric layer **530**. Referring to FIG. 3B, in some alternative embodiments, the first dielectric layer **530** may be over-grinded during the grinding process such that the top surfaces T.sub.CV1 of the first conductive vias **CV1** and the top surfaces T.sub.AM1 of the first alignment marks **AM1** are located at a level height higher than the top surface T.sub.530 of the first dielectric layer **530**. For example, the thickness of the first conductive vias **CV1** and the thickness of the first alignment marks **AM1** are both larger than the thickness of the first dielectric layer **530**. In some embodiments, the first conductive vias **CV1** and the first alignment marks **AM1** protrude from the top surface T.sub.530 of the first dielectric layer **530**.

(33) However, since the first dielectric layer **530** is formed by the grinding-back method, the height difference is negligible. For example, a distance between the top surfaces T.sub.530 of the first dielectric layer **530** and the top surfaces T.sub.CV1 of the first conductive vias **CV1** (the height difference) is less than 0.6 μm . Similarly, a distance between the top surfaces T.sub.530 of the first dielectric layer **530** and the top surfaces T.sub.AM1 of the first alignment mark **AM1** (the height difference) is also less than 0.6 μm .

(34) Referring back to FIG. 1J, in some embodiments, after the top surfaces T.sub.CV1 of the first conductive via **CV1** and the top surfaces T.sub.AM1 of the first alignment mark **AM1** are exposed, these surfaces are further grinded to render a smooth profile. For example, a roughness of the top surfaces T.sub.CV1 of the first conductive vias **CV1** ranges between 0.04 μm and 0.09 μm . Similarly, a roughness of the top surfaces T.sub.AM1 of the first alignment mark **AM1** also ranges between 0.04 μm and 0.09 μm . Since the first alignment marks **AM1** have smooth top surfaces T.sub.AM1 and the top surfaces T.sub.AM1 of the first alignment marks **AM1** are substantially coplanar with the top surface T.sub.530 of the first dielectric layer **530** adjacent thereto, better resolution of the first alignment marks **AM1** may be obtained by the machinery during the exposure/alignment process. As such, the subsequently formed elements may be accurately formed on the designated location, thereby enhancing the reliability of the InFO package **10**.

(35) In some embodiments, the first conductive vias **CV1**, the first alignment mark **AM1**, and the first dielectric layer **530** may constitute a first sub-layer of a subsequently formed redistribution structure **500** (shown in FIG. 1T). As illustrated in FIG. 1J, the first sub-layer is formed over the

encapsulant **400**, the dies **300**, and the conductive structures **200**. The first dielectric layer **530** wraps around the first conductive vias **CV1** and the first alignment marks **AM1**. That is, the first conductive vias **CV1** and the first alignment marks **AM1** are embedded in the first dielectric layer **530**. Referring to FIG. **1J**, since the first dielectric layer **530** wraps around sidewalls of the first alignment marks **AM1**, the first dielectric layer **530** is able to protect the sidewalls of the first alignment marks **AM1** from being damaged by the subsequent processes (i.e. etching process or the like). That is, in some embodiments, each of the first alignment marks **AM1** has substantially straight sidewalls. For example, an included angle formed between the sidewalls of the first alignment mark **AM1** and a virtual line extending along a direction perpendicular to the top surface **T.sub.AM1** of the first alignment mark **AM1** may range between 85° and 90° .

(36) Referring to FIG. **1K**, a seed material layer **512** is formed over the first sub-layer. The seed material layer **512** may be similar to the seed material layer **510**, so the detailed descriptions thereof are omitted herein. In some embodiments, the seed material layer **512** is blanketly formed to be in direct contact with the first dielectric layer **530**, the first conductive vias **CV1**, and the first alignment mark **AM1**. The seed material layer **512** is formed to locate in both of the active region **AR** and the border region **BR**.

(37) Referring to FIG. **1L**, a photoresist layer **PR2** is formed over the seed material layer **512**. In some embodiments, the photoresist layer **PR2** may be formed through spin-coating or other suitable formation methods. As illustrated in FIG. **1L**, the photoresist layer **PR2** has a plurality of openings **OP2** exposing at least a portion of the seed material layer **512**. In some embodiments, the precision of the locations of the openings **OP2** may be ensured by using the first alignment mark **AM1** as an alignment tool. In some embodiments, the openings **OP2** in the active region **AR** correspond to the locations of the first conductive vias **CV1**. For example, a vertical projection of the openings **OP2** in the active region **AR** along the direction perpendicular to the active surface **300c** of the dies **300** overlaps with the first conductive vias **CV1**. On the other hand, the openings **OP2** in the border region **BR** does not correspond to the locations of the first alignment marks **AM1**. For example, a vertical projection of the openings **OP2** in the border region **BR** along the direction perpendicular to the active surface **300c** of the dies **300** does not overlap with the first alignment marks **AM1**.

(38) Referring to FIG. **1L** and FIG. **1M**, a plurality of conductive patterns **540a**, **540b** are formed on the seed material layer **512**. In some embodiments, a conductive material (not shown) is filled into the openings **OP2** of the photoresist layer **PR2**. Thereafter, the photoresist layer **PR2** is removed to obtain the conductive patterns **540a**, **540b**. Upon removal of the photoresist layer **PR2**, portions of the seed material layer **512**, which are not covered by the conductive patterns **540a**, **540b**, are exposed. In some embodiments, the conductive material may be formed by a plating process. The plating process is, for example, electro-plating, electroless-plating, immersion plating, or the like. In some embodiments, the conductive material includes, for example, copper, copper alloys, or the like. The photoresist pattern layer **PR2** may be removed/stripped through, for example, etching, ashing, or other suitable removal processes. In some embodiments, the conductive patterns **540a** are located in the active region **AR** and the conductive patterns **540b** are located in the border region **BR**.

(39) Referring to FIG. **1N**, a photoresist layer **PR3** is formed over the seed material layer **512** and the conductive patterns **540a**, **540b**. In some embodiments, the photoresist layer **PR3** may be formed through spin-coating or other suitable formation methods. As illustrated in FIG. **1N**, the photoresist layer **PR3** has a plurality of openings **OP3** exposing at least a portion of the conductive patterns **540a**, **540b**. In some embodiments, the precision of the locations of the openings **OP3** may be ensured by using the first alignment mark **AM1** as an alignment tool. In some embodiments, two adjacent openings **OP3** in the border region **BR** may be closer than two adjacent openings **OP3** in the active region **AR**. For example, a distance between two adjacent openings **OP3** above the conductive patterns **540b** may be smaller than a distance between two adjacent openings **OP3**

above the conductive patterns **540a**. In some embodiments, multiple openings **OP3** in the border region **BR** exposes the same conductive pattern **540b** while each of the openings **OP3** in the active region **AR** exposes different conductive patterns **540a**.

(40) Referring to FIG. **1N** and FIG. **1O**, a plurality of conductive patterns **522a** and a plurality of conductive patterns **522b** are respectively formed on the conductive patterns **540a** and the conductive patterns **540b**. In some embodiments, a conductive material (not shown) is filled into the openings **OP3** of the photoresist layer **PR3**. Thereafter, the photoresist layer **PR3** is removed to obtain the conductive patterns **522a**, **522b**. In some embodiments, the conductive material may be formed by a plating process. The plating process is, for example, electro-plating, electroless-plating, immersion plating, or the like. In some embodiments, the conductive material includes, for example, copper, copper alloys, or the like. In some embodiments, the plating process of the conductive patterns **522a**, **522b** shares the same seed layer with the plating process of the conductive patterns **540a**, **540b**. That is, the seed material layer **512** may be utilized as a seed layer for plating for both of the conductive patterns **540a**, **540b** and the conductive patterns **522a**, **522b**. As a result, the conductive patterns **522a** and the conductive patterns **522b** are free of seed layer. That is, no seed layer exists between the conductive patterns **522a** and the conductive patterns **540a** and no seed layer exists between the conductive patterns **522b** and the conductive patterns **540b**. The photoresist pattern layer **PR3** may be removed/stripped through, for example, etching, ashing, or other suitable removal processes. In some embodiments, the conductive patterns **522a** are located in the active region **AR** and the conductive patterns **522b** are located in the border region **BR**.

(41) Referring to FIG. **1O** and FIG. **1P**, the seed material layer **512** that is not covered by the conductive patterns **540a**, **540b** is removed to render seed layers **512a**, **512b**. The seed layer **512a** is located in the active region **AR** and the seed layer **512b** is located in the border region **BR**. In some embodiments, the seed layer **512a** is sandwiched between the first conductive vias **CV1** and the conductive patterns **540a**. On the other hand, the seed layer **512b** is sandwiched between the first dielectric layer **530** and the conductive patterns **540b**. Moreover, the conductive patterns **540a** is sandwiched between the conductive patterns **522a** and the seed layer **512a**, and the conductive patterns **540b** is sandwiched between the conductive patterns **522b** and the seed layer **512b**. The exposed portions of the seed material layer **512** may be removed through an etching process. In some embodiments, the material of the conductive patterns **522a**, **522b**, **540a**, **540b** may be different from the material of the seed material layer **512**, so the exposed portion of the seed material layer **512** may be removed through selective etching.

(42) In some embodiments, the conductive patterns **540a** and the seed layer **512a** located in the active region **AR** are collectively referred to as first routing patterns **RP1**. In some embodiments, the conductive patterns **522a** located in the active region **AR** may be referred to as second conductive vias **CV2**. On the other hand, the conductive patterns **522b**, the conductive patterns **540b**, and the seed layer **512b** located in the border region **BR** may be collectively referred to as second alignment marks **AM2**. In some embodiments, the first routing pattern **RP1** and the second conductive vias **CV2** are located in the active region **AR**. On the other hand, the second alignment marks **AM2** are located in the border region **BR**. The first routing patterns **RP1** may include routing traces for signal transmission along the horizontal plane. The second conductive vias **CV2** may electrically connect the first routing patterns **RP1** with other subsequently formed elements. On the other hand, the second alignment marks **AM2** may ensure other subsequently formed elements are precisely formed on the designated location. In some embodiments, the second alignment marks **AM2** are electrically floating. For example, the second alignment marks **AM2** are electrically insulated from the first routing patterns **RP1**, the second conductive vias **CV2**, the first alignment mark **AM1**, the first conductive vias **CV1**, the conductive structures **200**, the vias **350** of the dies **300**, and the redistribution structure **100**. In some embodiments, the second alignment marks **AM2** are in physical contact with the first dielectric layer **530**. For example, the seed layer **512b** of the

second alignment marks AM2 may be directly in contact with the first dielectric layer 530. In some embodiments, the second alignment marks AM2 are not overlapped with the first alignment marks AM1. For example, a vertical projection of the second alignment marks AM2 along the direction perpendicular to the active surface 300c of the dies 300 does not overlap with the first alignment marks AM1. Unlike the first alignment marks AM1 being a dual-layered structure, the second alignment mark AM2 may be a triple-layered structure. In some embodiments, each first alignment mark AM1 includes multiple conductive patterns 520b stacked on top of multiple seed layer patterns (seed layer 510b). As illustrated in FIG. 1P, the conductive patterns 520b are separated from each other, and the seed layer patterns are also separated from each other. On the other hand, each first alignment mark AM2 includes multiple conductive patterns 522b stacked on top of a continuous conductive pattern 540b and a continuous seed layer 512b.

(43) As mentioned above, the distance between two adjacent openings OP3 above the conductive patterns 540b may be smaller than the distance between two adjacent openings OP3 above the conductive patterns 540a. Since the second conductive vias CV2 and the second alignment marks AM2 are formed by filling the conductive material into the openings OP3, the second conductive vias CV2 and the second alignment marks AM2 may have shapes corresponding to the contour of the openings OP3. For example, each of the second conductive vias CV2 may be a bulk pattern from a top view while each of the second alignment marks AM2 may be a grid pattern from a top view. That is, one second conductive via CV2 includes one conductive pattern 522a while one second alignment mark AM2 includes multiple conductive patterns 522b. It should be noted that the second alignment marks AM2 may also adapt the configurations illustrated in FIG. 2A to FIG. 2C.

(44) Referring to FIG. 1Q, a dielectric material layer 532a is formed over the first dielectric layer 530, the first conductive vias CV1, and the first alignment marks AM1 to encapsulate the first routing patterns RP1, the second conductive vias CV2, and the second alignment marks AM2. In other words, the first routing patterns RP1, the second conductive vias CV2, and the second alignment marks AM2 are not revealed and are well protected by the dielectric material layer 532a. The dielectric material layer 532a may be similar to the dielectric material layer 530a, so the detailed descriptions thereof are omitted herein.

(45) Referring to FIG. 1Q and FIG. 1R, a portion of the dielectric material layer 532a is removed to form a second dielectric layer 530 exposing top surfaces T.sub.CV2 of the second conductive vias CV2 and top surfaces T.sub.AM2 of the second alignment marks AM2. For example, the dielectric material layer 532a may be grinded until top surfaces T.sub.CV2 of the second conductive vias CV2 and top surfaces T.sub.AM2 of the second alignment marks AM2 are exposed. In some embodiments, the dielectric material layer 532a is grinded by a chemical mechanical polishing (CMP) process. As illustrated in FIG. 1R, the second dielectric layer 532 is stacked over the first dielectric layer 530.

(46) In some embodiments, the dielectric material layer 532a is grinded such that a top surface T.sub.532 of the first dielectric layer 532 is substantially coplanar with the top surfaces T.sub.CV2 of the second conductive vias CV2 and the top surfaces T.sub.AM2 of the second alignment marks AM2. For example, the top surfaces T.sub.CV2 of the second conductive vias CV2 are substantially coplanar with top surfaces of the conductive patterns 522b. In some alternative embodiments, due to grinding selectivity between different materials, a height difference may be seen between the top surface T.sub.532 of the second dielectric layer 532 and the top surfaces T.sub.CV2 of the second conductive vias CV2 and between the top surface T.sub.532 of the second dielectric layer 532 and the top surfaces T.sub.AM2 of the second alignment marks AM2. However, since the second dielectric layer 532 is formed by the grinding-back method, the height difference is negligible. For example, a distance between the top surfaces T.sub.532 of the second dielectric layer 532 and the top surfaces T.sub.CV2 of the second conductive vias CV2 (the height difference) is less than 0.6 μm . Similarly, a distance between the top surfaces T.sub.532 of the second dielectric

layer **532** and the top surfaces T.sub.AM2 of the second alignment marks AM2 (the height difference) is also less than 0.6 μm .

(47) In some embodiments, after the top surfaces T.sub.CV2 of the second conductive vias CV2 and the top surfaces T.sub.AM2 of the second alignment mark AM2 are exposed, these surfaces are further grinded to render a smooth profile. For example, a roughness of the top surfaces T.sub.CV2 of the second conductive vias CV2 ranges between 0.04 μm and 0.09 μm . Similarly, a roughness of the top surfaces T.sub.AM2 of the second alignment mark AM2 also ranges between 0.04 μm and 0.09 μm . Since the second alignment marks AM2 have smooth top surfaces T.sub.AM2 and the top surfaces T.sub.AM2 of the second alignment marks AM2 are substantially coplanar with the top surface T.sub.532 of the first dielectric layer **532** adjacent thereto, better resolution of the second alignment marks AM2 may be obtained by the machinery during the exposure/alignment process. As such, the subsequently formed elements may be accurately formed on the designated location, thereby enhancing the reliability of the InFO package **10**.

(48) In some embodiments, the first routing patterns RP1, the second conductive vias CV2, the second alignment marks AM2, and the second dielectric layer **532** may constitute a second sub-layer of the subsequently formed redistribution structure **500** (shown in FIG. 1T). In some embodiments, the second sub-layer is formed over the first sub-layer. The second dielectric layer **532** wraps around the first routing patterns RP1, the second conductive vias CV2, and the second alignment marks AM2. That is, the first routing patterns RP1, the second conductive vias CV2, and the second alignment marks AM2 are embedded in the second dielectric layer **532**. In some embodiments, the second conductive vias CV2 are disposed on the first routing patterns RP1. In some embodiments, the first routing patterns RP1 are sandwiched between the first conductive vias CV1 and the second conductive vias CV2. In some embodiments, the second conductive vias CV2 are free of seed layer.

(49) Referring to FIG. 1R, since the second dielectric layer **532** wraps around sidewalls of the second alignment marks AM2, the second dielectric layer **532** is able to protect the sidewalls of the second alignment marks AM2 from being damaged by the subsequent processes (i.e. etching process or the like). That is, in some embodiments, each of the second alignment marks AM2 has substantially straight sidewalls. For example, an included angle formed between the sidewalls of the second alignment mark AM2 and a virtual line extending along a direction perpendicular to the top surface T.sub.AM2 of the second alignment mark AM2 may range between 85° and 90°.

(50) Referring to FIG. 1S, a plurality of second routing patterns RP2 and a plurality of third alignment marks AM3 are respectively formed on the second conductive vias CV2 and the second dielectric layer **532**. Each of the second routing patterns RP2 includes a seed layer **514a** and a conductive pattern **542a**. Each of the third alignment marks AM3 includes a seed layer **542b** and a conductive pattern **514b**. In some embodiments, the second routing patterns RP2 may be formed by similar methods as that of the first routing pattern RP1 or the first conductive vias CV1 and the third alignment marks AM3 may be formed by similar methods as that of the first alignment mark AM1. Therefore, detailed descriptions of the second routing patterns RP2 and the third alignment marks AM3 are omitted herein. In some embodiments, the precision of the locations of the second routing patterns RP2 and the third alignment mark AM3 may be ensured by using the second alignment mark AM2 as an alignment tool. In some embodiments, the second routing patterns RP2 are located in the active region AR and the third alignment marks AM3 are located in the border region BR. The second routing patterns RP2 may include routing traces for signal transmission along the horizontal plane. On the other hand, the third alignment marks AM3 may ensure other subsequently formed elements are precisely formed on the designated location. Similar to the first alignment marks AM1 and the second alignment marks AM2, the third alignment marks AM3 may be electrically floating and may include a grid pattern. For example, each of the third alignment marks AM3 is constituted by multiple conductive patterns **542b**. It should be noted that the third alignment mark AM3 may also adapt the configurations illustrated in FIG. 2A to FIG. 2C.

(51) Referring to FIG. 1T, a third dielectric layer **534** is formed over the second sub-layer. For example, the third dielectric layer **534** is stacked on the second dielectric layer **532**. The third dielectric layer **534** has a plurality of openings **OP4**. In some embodiments, the precision of the locations of the openings **OP4** may be ensured by using the third alignment mark **AM3** as an alignment tool. In some embodiments, the openings **OP4** partially exposes the conductive patterns **542a** of the second routing patterns **RP2** and completely exposes the third alignment marks **AM3**. However, the disclosure is not limited thereto. In some alternative embodiments, the third dielectric layer **534** may completely cover the third alignment marks **AM3**. The third dielectric layer **534** may be formed by the following steps. First, a dielectric material layer (not shown) is formed over the second dielectric layer **532** to cover the second routing patterns **RP2** and the third alignment marks **AM3**. In some embodiments, a material of the dielectric material layer includes polyimide, epoxy resin, acrylic resin, phenol resin, BCB, PBO, or any other suitable polymer-based dielectric material. The dielectric material layer may be formed by suitable fabrication techniques, such as spin-on coating, chemical vapor deposition (CVD), plasma-enhanced chemical vapor deposition (PECVD), or the like. Thereafter, the dielectric material layer may be patterned through a photolithography process and an etching process to render the third dielectric layer **534** having the openings **OP4**.

(52) Referring to FIG. 1U, a plurality of third routing patterns **RP3** are formed on the second routing patterns **RP2** to obtain a redistribution structure **500**. In some embodiments, the third routing patterns **RP3** includes a seed layer **516a** and a plurality of conductive patterns **544a**. In some embodiments, the third routing patterns **RP3** are located in the active region **AR**. The third routing patterns **RP3** may be formed by the following steps. First, a first mask pattern (not shown) may be adapted to cover/protect the third alignment marks **AM3**. Subsequently, a seed material layer (not shown) extending into the openings **OP4** may be formed over the third dielectric layer **534**. The seed material layer may be formed through, for example, a sputtering process, a physical vapor deposition (PVD) process, or the like. In some embodiments, the seed material layer may include, for example, copper, titanium-copper alloy, or other suitable choice of materials. A second mask pattern (not shown) may then be formed on the seed material layer. The second mask pattern has openings exposing the seed material layer located inside of the openings **OP4**. In some embodiments, the openings of the second mask pattern also exposes portions of the seed material layer in proximity of the openings **OP4**. Thereafter, a conductive material (not shown) is filled into the openings of the second mask and the openings **OP4** of the third dielectric layer **534** by electroplating or deposition. Then, the first and second mask patterns and the seed material layer underneath the second mask pattern are removed to obtain the third routing patterns **RP3**.

(53) In some embodiments, the second routing patterns **RP2**, the third routing patterns **RP3**, the third alignment marks **AM3**, and the third dielectric layer **534** may be considered as a third sub-layer of the redistribution structure **500**. In some embodiments, the third routing patterns **RP3** may include a plurality of pads. In some embodiments, the above-mentioned pads includes a plurality of under-ball metallurgy (UBM) patterns for ball mount.

(54) As illustrated in FIG. 1U, the redistribution structure **500** includes the first dielectric layer **530**, the second dielectric layer **532**, the third dielectric layer **534**, the first conductive vias **CV1**, the second conductive vias **CV2**, the first routing patterns **RP1**, the second routing patterns **RP2**, the third routing patterns **RP3**, the first alignment marks **AM1**, the second alignment marks **AM2**, and the third alignment marks **AM3**. The first conductive vias **CV1** and the first alignment marks **AM1** are embedded in the first dielectric layer **530**. The second conductive vias **CV2**, the first routing patterns **RP1**, and the second alignment marks **AM2** are embedded in the second dielectric layer **532**. The second routing patterns **RP2** are embedded in the third dielectric layer **534** while the third routing patterns **RP3** are partially embedded in the third dielectric layer **534**. A portion of the first conductive vias **CV1** is in physical contact with the conductive structures **200** and the first routing patterns **RP1**. Another portion of the first conductive vias **CV1** is in physical contact with the vias

350 of the dies **300** and the first routing patterns **RP1**. That is, the first conductive vias **CV1** electrically connect the conductive structures **200**, the dies **300**, and the first routing patterns **RP1**. The second conductive vias **CV2** are in physical contact with the first routing patterns **RP1** and the second routing patterns **RP2**. That is, the second conductive vias electrically interconnect the first routing patterns **RP1** and the second routing patterns **RP2**. The second routing patterns **RP2** are in physical contact with the second conductive vias **CV2** and the third routing patterns **RP3**. That is, the second routing patterns **RP2** are electrically connected to the second conductive vias **CV2** and the third routing patterns **RP3**.

(55) In some embodiments, the redistribution structure **500** is referred to as a front-side redistribution structure. It should be noted that although the redistribution structure **500** is illustrated to have three sub-layers in FIG. **1U**, the disclosure is not limited thereto. In some alternative embodiments, the redistribution structure **500** may be constituted by more or less layers of sub-layers depending on the circuit design.

(56) Referring to FIG. **1V**, after the redistribution structure **500** is formed, a plurality of conductive terminals **600** are placed on the third routing patterns **RP3** (the UBM patterns) of the redistribution structure **500**. In some embodiments, the conductive terminals **600** are electrically connected to the redistribution structure **500**. In some embodiments, the conductive terminals **600** include solder balls. In some embodiments, the conductive terminals **600** may be placed on the UBM patterns through a ball placement process.

(57) Referring to FIG. **1V** and FIG. **1W**, after the conductive terminals **600** are formed on the redistribution structure **500**, the redistribution structure **100** is separated from the de-bonding layer **DB** and the carrier **100**. In some embodiments, the de-bonding layer **DB** (e.g., the LTHC release layer) may be irradiated by an UV laser such that the carrier **C** and the de-bonding layer **DB** may be peeled off. Nevertheless, the de-bonding process is not limited thereto. Other suitable de-carrier methods may be used in some alternative embodiments. After removing the de-bonding layer **DB** and the carrier **C**, the structure is flipped upside down and is placed on a tape **TP**.

(58) Referring to FIG. **1X**, a plurality of openings **OP5** are formed in the dielectric layer **104** to partially expose the redistribution conductive layer **102**. In some embodiments, when multiple redistribution conductive layers **102** are present, the openings **OP5** expose the bottommost redistribution conductive layer **102**. In some embodiments, the openings **OP5** are formed by a laser drilling process, a mechanical drilling process, a photolithography process, or other suitable processes. Thereafter, a plurality of conductive terminals **700** are formed over the redistribution structure **100**. In some embodiments, at least part of the conductive terminals **700** extends into the openings **OP5** to be in contact with the redistribution conductive layer **102**, thereby rendering electrical connection with the redistribution structure **100**. In some embodiments, the conductive terminals **700** are attached to the redistribution conductive layer **102** through a solder flux (not shown). In some embodiments, the conductive terminals **700** are, for example, solder balls. In some embodiments, the conductive terminals **700** may be disposed on the redistribution conductive layer **102** by a ball placement process and/or a reflow process.

(59) Referring to FIG. **1X** and FIG. **1Y**, the structure illustrated in FIG. **1X** is diced or singulated. Thereafter, the diced structure is removed from the tape **TP** to form a plurality of InFO packages **10**. In some embodiments, the dicing process or the singulation process typically involves dicing with a rotating blade or a laser beam. In other words, the dicing or singulation process is, for example, a laser cutting process, a mechanical cutting process, or other suitable processes.

(60) FIG. **4** is a schematic cross-sectional view illustrating a package-on-package (PoP) structure **1000**. Referring to FIG. **4**, in some embodiments, the InFO package **10** obtained in FIG. **1Y** may have a dual-side terminal design to accommodate other electronic components. For example, a sub-package **20** may be stacked on the InFO package **10**. The sub-package **20** is, for example, IC packages. The sub-package **20** is electrically connected to the InFO package **10** through the conductive terminals **700**. In some embodiments, after the sub-package **20** is stacked on the InFO

package **10**, a reflowing process is further performed to enhance the adhesion between the InFO package **10** and the sub-package **20**. It is noted that FIG. **4** merely serves as an exemplary illustration, and the disclosure is not limited thereto. In some alternative embodiments, other electronic devices such as an integrated fan-out (InFO) package, a memory device, a ball grid array (BGA), or a wafer may be stacked over the InFO package **10** in place of the sub-packages **20**.

(61) FIG. **5** is a cross-sectional view illustrating an InFO package **20** in accordance with some alternative embodiments of the disclosure. Referring to FIG. **5**, the InFO package **20** is similar to the InFO package **10** illustrated in FIG. **1Y**, so the detailed descriptions thereof are omitted herein. However, during the manufacturing process of the InFO package **20**, the alignment marks are formed within the scribe line. Therefore, after the singulation process, the alignment marks will be cut out from the InFO package **20**.

(62) FIG. **6A** to FIG. **6I** are schematic cross-sectional views illustrating intermediate stages of a manufacturing process of an InFO package **30** in accordance with some alternative embodiments of the disclosure. In some embodiments, the InFO package **30** may be manufactured by performing processes similar to the steps illustrated in FIG. **1A** to FIG. **1Y** except the alteration of the steps of forming the redistribution structure **500**. That is, the steps illustrated in FIG. **1F** to FIG. **1U** may be replaced by the steps illustrated in FIG. **6A** to FIG. **6H**.

(63) Referring to FIG. **6A**, the steps illustrated in FIG. **1A** to FIG. **1E** may be performed. Thereafter, a photoresist layer **PR1'** is formed over the seed material layer **510**. In some embodiments, the photoresist layer **PR1** may be formed through spin-coating or other suitable formation methods. As illustrated in FIG. **6A**, the photoresist layer **PR1'** has a plurality of openings **OP1'** exposing at least a portion of the seed material layer **510**. In some embodiments, the openings **OP1'** are located in the border region **BR**. On the other hand, the active region **AR** is free of the openings **OP1'**.

(64) Referring to FIG. **6A** and FIG. **6B**, a plurality of conductive patterns **520b** are formed on the seed material layer **510**. In some embodiments, a conductive material (not shown) is filled into the openings **OP1'** of the photoresist layer **PR1'**. Thereafter, the photoresist layer **PR1** is removed to obtain the conductive patterns **520b** located in the border region **BR**. Upon removal of the photoresist layer **PR1'**, portions of the seed material layer **510**, which are not covered by the conductive patterns **520b**, are exposed. In some embodiments, the conductive material may be formed by a plating process. The plating process is, for example, electro-plating, electroless-plating, immersion plating, or the like. In some embodiments, the conductive material includes, for example, copper, copper alloys, or the like. The photoresist pattern layer **PR1'** may be removed/stripped through, for example, etching, ashing, or other suitable removal processes.

(65) Referring to FIG. **6B** and FIG. **6C**, the seed material layer **510** that is not covered by the conductive patterns **520b** is removed to render seed layer **510b**. That is, the seed material layer **510** underneath the photoresist layer **PR1'** is removed. The exposed portions of the seed material layer **510** may be removed through an etching process. In some embodiments, the material of the conductive patterns **520b** may be different from the material of the seed material layer **510**, so the exposed portion of the seed material layer **510** may be removed through selective etching. In some embodiments, the seed layer **510b** may include a plurality of seed layer patterns. As illustrated in FIG. **6C**, the seed layer patterns are aligned with the conductive patterns **520b** along a direction perpendicular to the active surface **300c** of the die **300**. For example, sidewalls of each seed layer pattern are aligned with sidewalls of each conductive pattern **520b**.

(66) In some embodiments, the conductive patterns **520b** and the seed layer **510b** located in the border region **BR** may be collectively referred to as first alignment marks **AM1**. The first alignment marks **AM1** may ensure other subsequently formed elements are precisely formed on the designated location. In some embodiments, the first alignment marks **AM1** are electrically floating. For example, the first alignment marks **AM1** are electrically insulated from the conductive structures **200**, the vias **350** of the dies **300**, and the redistribution structure **100**. In some

embodiments, the first alignment marks AM1 are in physical contact with the encapsulant 400. For example, the seed layer 510b of the first alignment marks AM1 may be directly in contact with the encapsulant 400. In some embodiments, each of the first alignment marks AM1 may be a grid pattern from a top view. That is, one first alignment mark AM1 includes multiple conductive patterns 520b.

(67) Referring to FIG. 6D, a dielectric material layer 530a is formed over the encapsulant 400, the conductive structures 200, and the dies 300 to encapsulate the first alignment marks AM1. In other words, the first alignment marks AM1 are not revealed and are well protected by the dielectric material layer 530a. In some embodiments, a material of the dielectric material layer 530a includes polyimide, epoxy resin, acrylic resin, phenol resin, BCB, PBO, or any other suitable polymer-based dielectric material. The dielectric material layer 530a may be formed by suitable fabrication techniques, such as spin-on coating, chemical vapor deposition (CVD), plasma-enhanced chemical vapor deposition (PECVD), or the like.

(68) Referring to FIG. 6D and FIG. 6E, a portion of the dielectric material layer 530a is removed to form a first dielectric layer 530 exposing top surfaces T.sub.AM1 of the first alignment marks AM1. For example, the dielectric material layer 530a may be grinded until top surfaces T.sub.AM1 of the first alignment marks AM1 are exposed. In some embodiments, the dielectric material layer 530a is grinded by a chemical mechanical polishing (CMP) process.

(69) In some embodiments, the dielectric material layer 530a is grinded such that a top surface T.sub.530 of the first dielectric layer 530 is substantially coplanar with the top surfaces T.sub.AM1 of the first alignment marks AM1. However, the disclosure is not limited thereto. In some alternative embodiments, the top surface T.sub.530 of the first dielectric layer 530 may be located at a level height different from the top surfaces T.sub.AM1 of the first alignment marks AM1. Nevertheless, the height difference may be negligible. In some embodiments, after the top surfaces T.sub.AM1 of the first alignment mark AM1 are exposed, these surfaces are further grinded to render a smooth profile. Since the first alignment marks AM1 have smooth top surfaces T.sub.AM1 and the top surfaces T.sub.AM1 of the first alignment marks AM1 are substantially coplanar with the top surface T.sub.530 of the first dielectric layer 530 adjacent thereto, better resolution of the first alignment marks AM1 may be obtained by the machinery during the exposure/alignment process. As such, the subsequently formed elements may be accurately formed on the designated location, thereby enhancing the reliability of the InFO package 30.

(70) Referring to FIG. 6F, the first dielectric layer 530 is patterned to form a plurality of openings OP2' in the active region AR. In some embodiments, the openings OP2' expose the conductive structures 200 and the vias 350 of the dies 300 located underneath the first dielectric layer 530. In other words, the locations of the openings OP2' correspond to the locations of the conductive structures 200 and vias 350. In some embodiments, the border region BR is free of openings OP2'. In some embodiments, the precision of the locations of the openings OP2' may be ensured by using the first alignment mark AM1 as an alignment tool. The first dielectric layer 530 may be patterned through a photolithography process and an etching process.

(71) Referring to FIG. 6G, a plurality of first routing patterns RP1' are formed over the first dielectric layer 530. In some embodiments, the first routing patterns RP1' extends into the openings OP2' to be directly in contact with the conductive structures 200 and the vias 350 of the die 300. In some embodiments, each first routing pattern RP1' includes a seed layer 510c and a conductive pattern 520c. In some embodiments, the first routing pattern RP1' may be formed by the following manner. First, a seed material layer (not shown) may be formed over the first dielectric layer 530. The seed material layer is formed in a conformal manner such that the seed material layer extends into the openings OP2' of the first dielectric layer 530 to cover a bottom surface and sidewalls of the openings OP2'. The seed material layer may be formed through, for example, a sputtering process, a physical vapor deposition (PVD) process, or the like. In some embodiments, the seed material layer may include, for example, copper, titanium-copper alloy, or other suitable choice of

materials.

(72) Thereafter, a photoresist pattern layer (not shown) is formed over the seed material layer. In some embodiments, the photoresist pattern layer exposes the seed material layer located in the openings OP2' and exposes at least a portion of the seed material layer located on the first dielectric layer 530 and around the openings OP2'. Subsequently, a conductive material (not shown) is deposited onto the exposed seed material layer using the photoresist pattern layer as a mask to form the conductive patterns 520c. In some embodiments, the conductive material may be formed by a plating process. The plating process is, for example, electro-plating, electroless-plating, immersion plating, or the like. In some embodiments, the conductive material includes, for example, copper, copper alloys, or the like. After forming the conductive patterns 520c, the photoresist pattern layer is removed to expose portions of the seed material layer not covered by the conductive patterns 520c. The portions of the seed material layer not covered by the conductive patterns 520c are then removed to obtain the seed layer 510c of the first routing patterns RP1'. As illustrated in FIG. 6A to FIG. 6G, the first alignment marks AM1 are formed prior to the formation of the first routing patterns RP1'.

(73) Referring to FIG. 6H, the process similar to the steps shown in FIG. 1L to FIG. 1R (except the first routing patterns RP1 and the second conductive vias CV2 are not formed) and FIG. 6A to FIG. 6G may be repeated to obtain the second routing patterns RP2', the second alignment marks AM2, and the second dielectric layer 532. Similar to the first routing patterns RP1', each second routing pattern RP2' also includes a seed layer 514c and a conductive pattern 542c. In some embodiments, the process similar to the steps shown in FIG. 1S to FIG. 1U (except the second routing patterns RP2 are not formed) may be adapted to form the third routing patterns RP3, the third alignment marks AM3, and the third dielectric layer 534. In some embodiments, each third routing patterns RP3 includes a seed layer 516a and a conductive pattern 544a. In some embodiments, the first routing patterns RP1', the second routing patterns RP2, and the third routing patterns RP3 are electrically connected to each other. In some embodiments, the first routing patterns RP1', the second routing patterns RP2', and the third routing patterns RP3 are also electrically connected to the conductive structures 200 and the vias 350 of the die 300. In some embodiments, the second routing patterns RP2' are directly in contact with the first routing patterns RP1', and the third routing patterns RP3 are directly in contact with the second routing patterns RP2'. As illustrated in FIG. 6H, a portion of the first routing patterns RP1' is embedded in the first dielectric layer 530 and another portion of the first routing patterns RP1' is embedded in the second dielectric layer 532. Similarly, a portion of the second routing patterns RP2' is embedded in the second dielectric layer 532 and another portion of the second routing patterns RP2' is embedded in the third dielectric layer 543.

(74) Referring to FIG. 6I, process similar to the steps shown in FIG. 1V to FIG. 1Y may be performed to obtain the InFO package 30.

(75) In accordance with some embodiments of the disclosure, an integrated fan-out (InFO) package includes an encapsulant, a die, a plurality of conductive structures, and a redistribution structure. The die and the conductive structures are encapsulated by the encapsulant. The conductive structures surround the die. The redistribution structure is disposed on the encapsulant. The redistribution structure includes a plurality of routing patterns, a plurality of conductive vias, and a plurality of alignment marks. The conductive vias interconnects the routing patterns. At least one of the alignment mark is in physical contact with the encapsulant.

(76) In accordance with some embodiments of the disclosure, an integrated fan-out (InFO) package includes an encapsulant, a die, a plurality of conductive structures, and a redistribution structure. The die and the conductive structures are encapsulated by the encapsulant. The conductive structures surround the die. The redistribution structure is disposed on the encapsulant. The redistribution structure includes a first dielectric layer, a second dielectric layer, a first alignment mark, and a second alignment mark. The second dielectric layer is stacked on the first dielectric

layer. The first alignment mark is embedded in the first dielectric layer, and the second alignment mark is embedded in the second dielectric layer. The first alignment mark includes a first seed layer and a plurality of first conductive patterns. The first conductive patterns are stacked on the first seed layer. The second alignment mark includes a second seed layer, a second conductive pattern, and a plurality of third conductive patterns. The second conductive pattern is sandwiched between the second seed layer and the third conductive patterns.

(77) In accordance with some embodiments of the disclosure, a manufacturing method of an integrated fan-out (InFO) package includes at least the following steps. A carrier is provided. A die and a plurality of conductive structures are formed over the carrier. The conductive structures surround the die. The die and the conductive structures are encapsulated by an encapsulant. A redistribution structure is formed over the encapsulant. The redistribution structure includes a first alignment mark physically in contact with the encapsulant.

(78) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. An integrated fan-out (InFO) package, comprising: a die; an encapsulant laterally encapsulating the die; and a redistribution structure disposed on the encapsulant, wherein the redistribution structure comprises a plurality of routing patterns and a plurality of alignment marks, the plurality of routing patterns is electrically connected to the die, the plurality of alignment marks surrounds the plurality of routing patterns, the plurality of alignment marks is electrically insulated from the die and the plurality of routing patterns, at least one of the plurality of alignment marks is in physical contact with the encapsulant, and the plurality of alignment marks located at different level heights is arranged in a non-overlapping manner vertically.
2. The InFO package according to claim 1, wherein each of the plurality of alignment marks comprises a grid pattern.
3. The InFO package according to claim 1, further comprising a plurality of conductive terminals over the redistribution structure, wherein the plurality of conductive terminals is electrically connected to the redistribution structure.
4. The InFO package according to claim 1, wherein the redistribution structure further comprises a plurality of dielectric layers stacked on each other, at least one of the plurality of dielectric layers wraps around the corresponding routing pattern and the corresponding alignment mark, and a top surface of the at least one of the plurality of dielectric layers is substantially coplanar with a top surface of the corresponding alignment mark.
5. The InFO package according to claim 4, wherein the at least one of the plurality of alignment marks penetrates through the corresponding dielectric layer.
6. The InFO package according to claim 1, wherein the redistribution structure further comprises a plurality of dielectric layers stacked on each other, at least one of the plurality of alignment mark is embedded in at least one of the plurality of dielectric layers, and a distance between a top surface of the at least one of the plurality of dielectric layers and a top surface of the at least one of the plurality of alignment marks is less than 0.6 μm .
7. The InFO package according to claim 1, wherein at least one of the plurality of alignment mark comprises a seed layer, a first conductive pattern, and a plurality of second conductive patterns, and

the first conductive pattern is sandwiched between the plurality of second conductive patterns and the seed layer.

8. An integrated fan-out (InFO) package, comprising: a die; a redistribution structure disposed on the die, wherein the redistribution structure comprises: a first dielectric layer; a first alignment mark penetrating through the first dielectric layer, wherein the first alignment mark comprises a first seed layer and a plurality of first conductive patterns stacked on the first seed layer, and the first alignment mark is electrically insulated from the die; a second dielectric layer stacked on the first dielectric layer and the first alignment mark; and a second alignment mark penetrating through the second dielectric layer, wherein the second alignment mark comprises a second seed layer, a second conductive pattern, and a plurality of third conductive patterns stacked in sequential order, and the second alignment mark is electrically insulated from the die.

9. The InFO package according to claim 8, further comprising: an encapsulant laterally encapsulating the die, wherein the first seed layer of the first alignment mark is in physical contact with the encapsulant.

10. The InFO package according to claim 8, wherein the first seed layer comprises a plurality of first seed layer patterns, and sidewalls of each of the plurality of first seed layer patterns are aligned with sidewalls of each of the plurality of first conductive patterns.

11. The InFO package according to claim 8, wherein the first alignment mark and the second alignment mark are electrically floating.

12. The InFO package according to claim 8, wherein the redistribution structure further comprises: a plurality of first conductive vias embedded in the first dielectric layer, wherein the plurality of first conductive vias comprises a seed layer; a plurality of first routing patterns embedded in the second dielectric layer and being stacked on the plurality of first conductive vias, wherein the plurality of first routing patterns comprises a seed layer; and a plurality of second conductive vias embedded in the second dielectric layer and being free of seed layer, wherein the plurality of second conductive vias are disposed on the plurality of first routing patterns.

13. The InFO package according to claim 12, wherein top surfaces of the plurality of first conductive vias are substantially coplanar with top surfaces of the plurality of first conductive patterns of the first alignment mark, and top surfaces of the plurality of second conductive vias are substantially coplanar with top surfaces of the plurality of third conductive patterns of the second alignment mark.

14. The InFO package according to claim 12, wherein the InFO package has an active region and a border region surrounding the active region, the border region is devoid of the die, the plurality of first conductive vias, the plurality of second conductive vias, and the plurality of first routing patterns are located in the active region, the first alignment mark and the second alignment mark are located in the border region, and the first alignment mark and the second alignment mark are arranged in a non-overlapping manner vertically in the same border region.

15. The InFO package according to claim 8, further comprising a plurality of conductive terminals over the redistribution structure, wherein the plurality of conductive terminals is electrically connected to the redistribution structure.

16. A manufacturing method of an integrated fan-out (InFO) package having an active region and a border region surrounding the active region, comprising: providing a die in the active region; laterally encapsulating the die by an encapsulant; and forming a redistribution structure over the encapsulant, comprising: forming a first sub-layer over the encapsulant and the die, wherein the first sub-layer comprises a plurality of first conductive vias and a first alignment mark, the plurality of first conductive vias is located in the active region and the first alignment mark is located in the border region, and the first alignment mark is physically in contact with the encapsulant; and forming a second sub-layer over the first sub-layer, wherein the second sub-layer comprises a plurality of routing patterns, a plurality of second conductive vias, and a second alignment mark, the plurality of routing patterns and the plurality of second conductive vias are located in the active

region and the second alignment mark is located in the border region, the first alignment mark and the second alignment mark are arranged in a non-overlapping manner vertically in the same border region, and the border region is devoid of the die.

17. The method according to claim 16, wherein the step of forming the first sub-layer comprises: forming a seed material layer over the encapsulant and the die; forming a photoresist layer over the seed material layer, wherein the photoresist layer comprises a plurality of openings exposing at least a portion of the seed material layer; filling a conductive material into the plurality of openings of the photoresist layer to form a plurality of conductive patterns; removing the photoresist layer and portions of the seed material layer underneath the photoresist layer to form the plurality of first conductive vias and the first alignment mark; forming a dielectric material layer over the encapsulant and the die to encapsulate the plurality of first conductive vias and the first alignment mark; and removing a portion of the dielectric material layer to form a dielectric layer exposing a top surface of the plurality of first conductive vias and a top surface of the first alignment mark.

18. The method according to claim 17, wherein a top surface of the dielectric layer is substantially coplanar with the top surface of the plurality of first conductive vias and the top surface of the first alignment mark.

19. The method according to claim 16, wherein the step of forming the second sub-layer comprises: forming a seed material layer over the first-sub layer; forming a first photoresist layer over the seed material layer, wherein the first photoresist layer comprises a plurality of first openings exposing at least a portion of the seed material layer; filling a first conductive material into the plurality of first openings of the first photoresist layer to form a plurality of first conductive patterns; removing the first photoresist layer; forming a second photoresist layer over the seed material layer and the plurality of first conductive patterns, wherein the second photoresist layer comprises a plurality of second openings exposing at least a portion of the plurality of first conductive patterns; filling a second conductive material into the plurality of second openings of the second photoresist layer to form a plurality of second conductive patterns; removing the second photoresist layer and portions of the seed material layer exposed by the plurality of first conductive patterns to form the plurality of routing patterns, the plurality of second conductive vias, and the second alignment mark, wherein the plurality of second conductive vias is disposed on the plurality of routing patterns; forming a dielectric material layer over the first-sub layer to encapsulate the plurality of routing patterns, the plurality of second conductive vias, and the second alignment mark; and removing a portion of the dielectric material layer to form a dielectric layer exposing a top surface of the plurality of second conductive vias and a top surface of the second alignment mark.

20. The method according to claim 19, wherein a top surface of the dielectric layer is substantially coplanar with the top surface of the plurality of second conductive vias and the top surface of the second alignment mark.
