

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250278120

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

SIM; Jin Gyu et al.

DISPLAY DEVICE INCLUDING A COVER WINDOW HAVING A PATTERNED PORTION AND A METHOD FOR FABRICATING THE SAME

Abstract

A display device includes: a display panel including a folding area and a first and second non-folding areas; and a cover window on the display panel and having a patterned portion overlapping the folding area, and including a plurality of first concave grooves and a plurality of second concave grooves, wherein each of the plurality of first and second concave grooves includes an inner wall that extends from a surface of the cover window and a curved surface that extends from the inner wall, wherein an angle formed by the surface of the cover window and the inner wall ranges from about 80 degrees to about 89 degrees, wherein a radius of curvature at an end of the curved surface is greater than about 10 μm and less than about 30 μm , and wherein the patterned portion has a width in a first direction of the cover window.

Inventors: SIM; Jin Gyu (Yongin-si, KR), KANG; Byung Hoon (Yongin-si, KR), KIM; Sang Hoon (Yongin-si, KR), LEE; Hyun Ji (Yongin-si, KR), JUNG; Tae Hyeog (Yongin-si, KR), HWANG; Seong Jin (Yongin-si, KR)

Applicant: SAMSUNG DISPLAY CO., LTD. (Yongin-si, KR)

Family ID: 96827164

Appl. No.: 18/950670

Filed: November 18, 2024

Foreign Application Priority Data

KR 10-2024-0029642

Feb. 29, 2024

Publication Classification

Int. Cl.: G06F1/16 (20060101)

Background/Summary

[0001] This application claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2024-0029642, filed on Feb. 29, 2024 in the Korean Intellectual Property Office, the disclosure of which is incorporated by reference herein in its entirety.

TECHNICAL FIELD

[0002] Embodiments of the present invention relate to a display device and a method for fabricating the same, and more particularly, to a display device including a cover window having a patterned portion and a method for fabricating the same.

DISCUSSION OF THE RELATED ART

[0003] As the information-oriented society evolves, various desires of display devices are ever increasing. For example, display devices are being employed by a variety of electronic devices such as smart phones, digital cameras, laptop computers, navigation devices, and smart televisions.

[0004] Recently, to increase portability of the display device and provide a wider display screen, a bendable display device, in which the display area can be bent, or a foldable display device, in which the display area can be folded is currently under development.

[0005] Regarding the foldable display devices, there is a trend to use patterned glass to ensure impact resistance and flexibility, which are desirable characteristics for foldable display devices.

[0006] For example, the patterned glass used has a non-penetrating zigzag pattern. In the process of forming such a pattern, the state in which the foldable display device is folded should be considered, and the pattern should be formed with a consistent arrangement. Currently, the pattern formation on the glass is under development to provide increased impact resistance and increased flexibility, without defects such as abnormal folding and warpage.

SUMMARY

[0007] According to an embodiment of the present invention, a display device includes: a display panel including a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on second side of the folding area; and a cover window located on the display panel and having a patterned portion formed to overlap the folding area, wherein the patterned portion includes a plurality of first concave grooves and a plurality of second concave grooves, wherein the plurality of first concave grooves are formed in a first surface of the cover window, and the plurality of second concave grooves are formed in a second surface of the cover window that is opposite to the first surface and faces the display panel, wherein each of the plurality of first and second concave grooves includes an inner wall that extends from the first surface or the second surface of the cover window and a curved surface that extends from the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm , and wherein the patterned portion has a width in a first direction of the cover window, wherein the width is calculated by a following equation: $L \leq \pi(r+T)+1$, wherein r denotes a radius of curvature of the cover window disposed at a position overlapping with the folding area when the display panel is folded, wherein T denotes a thickness of the cover window, and L denotes the width of the patterned portion.

[0008] In an embodiment of the present invention, the radius of curvature at the end of the curved surface is smaller than the radius of curvature of the curved surface at a boundary between the

inner wall and the curved surface.

[0009] In an embodiment of the present invention, the first concave groove further includes a chamfered surface that is disposed between the inner wall of the first concave groove and the first surface of the cover window.

[0010] In an embodiment of the present invention, a minimum length of the chamfered surface from the inner wall of the first concave groove to the first surface of the cover window ranges from about 2 μm to 10 μm .

[0011] In an embodiment of the present invention, an angle formed by the first surface of the cover window and the chamfered surface is smaller than an angle that is formed by the first surface of the cover window and the inner wall of the first concave groove.

[0012] In an embodiment of the present invention, the plurality of first concave grooves and the plurality of second concave grooves have a same shape as each other, wherein the first concave grooves are recessed from the first surface toward the second surface, and wherein the second concave grooves are recessed from the second surface toward the first surface.

[0013] In an embodiment of the present invention, the first concave grooves and the second concave grooves are alternately arranged with each other.

[0014] In an embodiment of the present invention, each of the first concave grooves and the second concave grooves has a semicircular shape or a polygonal shape.

[0015] In an embodiment of the present invention, a number of the first concave grooves is greater than a number of the second concave grooves.

[0016] In an embodiment of the present invention, the number of the first concave grooves is odd.

[0017] According to an embodiment of the present invention, a display device includes: a display panel including a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on a second side of the folding area; and a cover window located on the display panel and having a pattern portion overlapping the folding area, wherein the pattern portion includes a plurality of first concave grooves and a plurality of second concave grooves, wherein the plurality of first concave grooves are formed in a first surface of the cover window, and the plurality of second concave grooves are formed in a second surface of the cover window opposite to the first surface and facing the display panel, wherein each of the plurality of first and second concave grooves includes an inner wall that extends from the first surface or the second surface of the cover window, a curved surface that extends from the inner wall, and a chamfered surface located adjacent to the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, and wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm .

[0018] In an embodiment of the present invention, a minimum length of the chamfered surface from the inner wall to the first surface of the cover window ranges from about 2 μm to 10 μm .

[0019] In an embodiment of the present invention, an angle formed by the first surface of the cover window and the chamfered surface is smaller than an angle that is formed by the first surface of the cover window and the inner wall of the first concave groove.

[0020] In an embodiment of the present invention, the radius of curvature at the end of the curved surface is smaller than the radius of curvature of the curved surface at a boundary between the inner wall and the curved surface.

[0021] In an embodiment of the present invention, the plurality of first concave grooves and the plurality of second concave grooves have a same shape as each other, wherein the first concave grooves are recessed from the first surface toward the second surface, and wherein the second concave grooves are recessed from the second surface toward the first surface.

[0022] In an embodiment of the present invention, the first concave grooves and the second concave grooves are alternately arranged with each other.

[0023] In an embodiment of the present invention, a number of the first concave grooves is greater

than a number of the second concave grooves.

[0024] According to an embodiment of the present invention, a method for fabricating a display device includes: preparing a cover window for protecting a display panel including a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on a second side of the folding area; and forming a patterned portion in the cover window to overlap with the folding area, wherein the forming of the patterned portion in the cover window includes: forming a plurality of first concave grooves in a first surface of the cover window; and forming a plurality of second concave grooves in a second surface of the cover window that is opposite to the first surface, wherein each of the plurality of first and second concave grooves includes an inner wall that extends from the first surface or the second surface of the cover window and a curved surface that extends from the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm , and wherein the patterned portion has a width in a first direction of the cover window, wherein the width is calculated by a following equation: $L \leq \pi(r+T)+1$, wherein r denotes a radius of curvature of the cover window disposed at a position overlapping with the folding area when the display panel is folded, wherein T denotes a thickness of the cover window, and L denotes the width of the patterned portion.

[0025] In an embodiment of the present invention, the method further includes forming a chamfered surface in each of the first and second concave grooves by chamfering.

[0026] In an embodiment of the present invention, the first and second concave grooves are formed by laser-induced deep etching (LIDE).

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0027] The above and other aspects and features of the present invention will become more apparent by describing in detail embodiments thereof with reference to the attached drawings, in which:

[0028] FIG. 1 is a perspective view of a display device according to an embodiment of the present invention when it is unfolded.

[0029] FIG. 2 is a perspective view showing the display device of FIG. 1 when it is folded.

[0030] FIG. 3 is an exploded perspective view of a display device according to an embodiment of the present invention.

[0031] FIG. 4 is a view showing a side of the display device according to an embodiment of the present invention.

[0032] FIG. 5 is a cross-sectional view of the display panel of FIGS. 3 and 4.

[0033] FIG. 6 is an enlarged cross-sectional view of a patterned portion of FIGS. 3 and 4.

[0034] FIG. 7 is an enlarged cross-sectional view of a part of the patterned portion of FIG. 6.

[0035] FIG. 8 is an enlarged cross-sectional view of the first and second concave grooves of FIG. 7.

[0036] FIG. 9 is a view showing the folding state of the cover glass when it is folded together with the display panel.

[0037] FIG. 10 is a view showing stress and strain test results according to the width L of the pattern portion of the cover window.

[0038] FIG. 11 is a view showing test results according to the radius of curvature of the concave groove of FIG. 8.

[0039] FIG. 12 is a view showing chamfered surfaces formed in the first and second concave grooves of FIG. 8.

[0040] FIG. 13 is a view showing the test results of impact resistance of the chamfered surface of FIG. 12.

[0041] FIG. 14 is a flowchart for illustrating a method for fabricating a display device according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0042] The present invention will now be described more fully hereinafter with reference to the accompanying drawings. The present invention may, however, be embodied in different forms and should not be construed as limiting of the present invention. The same reference numbers may indicate the same components throughout the specification and drawings, and thus, repetitive descriptions may be omitted. In the attached figures, various thicknesses, lengths, and angles are shown and while the arrangement shown does indeed represent an embodiment of the present disclosure, it is to be understood that modifications of the various thicknesses, lengths, and angles may be possible within the spirit and scope of the present disclosure and the present disclosure is not necessarily limited to the particular thicknesses, lengths, and angles shown.

[0043] It will also be understood that when a layer is referred to as being “on” another layer, it can be directly on the other layer, or intervening layers may also be present.

[0044] Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, in the example, terms “below” and “beneath” may encompass both an orientation of above, below and beneath. The device may be otherwise oriented (e.g., rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may be interpreted accordingly.

[0045] It will be understood that, although the terms “first,” “second,” etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. For instance, a first element discussed below could be termed a second element without departing from the spirit and scope of the present invention. Similarly, the second element could also be termed the first element.

[0046] Features of each of various embodiments of the present invention may be partially or entirely combined with each other and may technically variously interwork with each other, and respective embodiments may be implemented independently of each other or may be implemented together in association with each other.

[0047] Hereinafter, embodiments of the present invention will be described with reference to the accompanying drawings.

[0048] FIG. 1 is a perspective view of a display device according to an embodiment of the present invention when it is unfolded. FIG. 2 is a perspective view showing the display device of FIG. 1 when it is folded.

[0049] FIG. 1 shows a first state of the display device 10 when it is not folded along folding lines FL1 and FL2, and FIG. 2 shows a second state of the display device 10 when it is folded along the folding lines FL1 and FL2.

[0050] Referring to FIGS. 1 to 2, a display device 10 according to an embodiment of the present invention is for displaying moving images and/or still images. The display device 1 may be used as the display screen of portable electronic devices such as a mobile phone, a smart phone, a tablet PC, a smart watch, a watch phone, a mobile communications terminal, an electronic notebook, an electronic book, a portable multimedia player (PMP), a navigation device and a ultra mobile PC (UMPC), as well as the display screen of various products such as a television, a notebook, a monitor, a billboard and the Internet of Things (IoT).

[0051] Referring to FIGS. 1 and 2, a first direction DR1 may refer to a direction parallel to a side of the display device 10, for example, the horizontal direction of the display device 10 when viewed from the top. A second direction DR2 may refer to a direction parallel to another side of the display device 10 that meets the side of the display device 10, for example, the vertical direction of the display device 10 when viewed from the top. A third direction DR3 may refer to the thickness direction of the display device 10. For example, the first and second directions DR1 and DR2 may extend parallel to a plane of a surface of the display device 10, and the first direction DR1 intersects the second direction DR2. For example, the third direction DR3 is substantially perpendicular to the first and second directions DR1 and DR2.

[0052] The display device 10 may have a quadrangular shape, such as a rectangular shape when viewed from the top. Each of the corners of the display device 10 may form a right angle or may be rounded when viewed from the top. The front surface of the display device 10 may include two shorter sides extended in the first direction DR1 and two longer sides extended in the second direction DR2.

[0053] The display device 10 includes a display area DA and a non-display area NDA. The shape of the display area DA may follow the shape of the display device 10 when viewed from the top. For example, when the display device 10 has a rectangular shape when viewed from the top, the display area DA may also have a rectangular shape when viewed from the top.

[0054] The display area DA may include a plurality of pixels to display images. The non-display area NDA might not include pixels and thus might not display images. The non-display area NDA may be disposed around the display area DA. The non-display area NDA may surround the display area DA, but embodiments of the present invention is not limited thereto. For example, the display area DA may be partially surrounded by the non-display area NDA.

[0055] The display device 10 is configured to be in a first state, which is an unfolded state, or a second state, which is a bent or folded state. The display device 10 may be folded inward so that a first part of the display area DA faces a second part of the display area DA. For example, the display device 10 may be folded in an in-folding manner, as shown in FIG. 2. In this instance, a part of the front surface of the display device 10 may face another part of the display device 10 when the display device 10 is folded. In addition, the display device 10 may be folded outward (e.g., an out-folding manner) such that a part of the rear surface of the display device 10 faces another part of the rear surface of the display device 10 when it is folded.

[0056] The display device 10 may include a folding area FDA, a first non-folding area NFA1, and a second non-folding area NFA2. The display device 10 can be bent or folded at the folding area FDA, while it cannot be bent or folded at the first non-folding area NFA1 and the second non-folding area NFA2. That is to say, the first non-folding area NFA1 and the second non-folding area NFA2 may be flat areas of the display device 10.

[0057] The first non-folding area NFA1 may be disposed at a first side of the folding area FDA. For example, the first non-folding area NFA1 may be disposed at the lower side of the folding area FDA. The second non-folding area NFA2 may be disposed at a second side, opposite to the first side, of the folding area FDA. For example, the second non-folding area NFA2 may be disposed at the upper side of the folding area FDA. The folding area FDA may be defined by the first folding line FL1 and the second folding line FL2, where the display device 10 can be bent with a predetermined curvature. The first folding line FL1 may be the boundary between the folding area FDA and the first non-folding area NFA1, and the second folding line FL2 may be the boundary between the folding area FDA and the second non-folding area NFA2.

[0058] Each of the display area DA and the non-display area NDA may overlap at least one of the folding area FDA, the first non-folding area NFA1, or the second non-folding area NFA2. In the example shown in FIGS. 1 and 2, each of the display area DA and the non-display area NDA overlaps the folding area FDA, the first non-folding area NFA1 and the second non-folding area NFA2.

[0059] FIG. 3 is an exploded perspective view showing a display device according to an embodiment of the present invention. FIG. 4 is a view showing a side of the display device according to the embodiment of the present invention.

[0060] Referring to FIGS. 3 and 4, a display device **10** according to an embodiment of the present invention may include an upper protection member **100**, a cover window **200**, a first adhesive member **300**, a display panel **400**, and a panel protection member **500**.

[0061] The upper protection member **100** may be disposed on the front surface of the cover window **200**. The upper protection member **100** may be attached on the front surface of the cover window **200**. The upper protection member **100** may perform at least one of an anti-scattering function when the cover window **200** is broken, a shock absorption function, an anti-scratch function, an anti-fingerprint function, or an anti-glare function.

[0062] A light-blocking pattern may be formed on the rear surface of the upper protection member **100**. The light-blocking pattern may be disposed at or adjacent to the edge of the upper protection member **100**. The light-blocking pattern may include a light-blocking material that can block light. For example, the light-blocking pattern may be an inorganic black pigment such as carbon black, organic black pigment, or an opaque metallic substance

[0063] The cover window **200** may be attached on the front surface of the display panel **400** by the first adhesive member **300**. The cover window **200** may be made of a transparent material, and may be, for example, glass or plastic. For example, the cover window **200** may be, but is not limited to, an ultra-thin glass (UTG) having a thickness of about 0.1 mm or less or a transparent polyimide film.

[0064] The first adhesive member **300** may be located between the cover window **200** and the display panel **400** to attach the cover window **200** to the display panel **400**, and may be a transparent adhesive film or a transparent adhesive resin.

[0065] The display panel **400** may be a panel for displaying images. The display panel **400** may be, for example, an organic light-emitting display panel including an organic light-emitting layer, a quantum-dot light-emitting display panel including a quantum-dot light-emitting layer, an inorganic light-emitting display panel using inorganic semiconductor elements as the light-emitting elements, and a micro light-emitting display panel using micro light-emitting diodes as the light-emitting elements. In the following description, as an example, an organic light-emitting display panel is employed as the display panel **400**. It is, however, to be understood that the present invention is not limited thereto.

[0066] The panel protection member **500** may be disposed on the rear surface of the display panel **400**. The panel protection member **500** can support the display panel **400** and protect the rear surface of the display panel **400**. The panel protection member **500** may be made of plastic such as polyethylene terephthalate and polyimide, or glass. Although the panel protection member **500** is disposed in the folding area FDA of the display device **10** in the example of FIGS. 3 and 4, the embodiments of the present invention are not limited thereto. For example, the panel protection film **500** may be removed from the folding area FDA of the display device **10** so that the display device **10** can be folded smoothly.

[0067] FIG. 5 is a cross-sectional view of the display panel of FIGS. 3 and 4.

[0068] Referring to FIG. 5, in the display panel **400**, a display layer DISL may be disposed on a substrate SUB.

[0069] The display layer DISL may include a thin-film transistor layer TFTL, an emission material layer EML, and an encapsulation layer TFEL.

[0070] The thin-film transistor layer TFTL may be disposed on the substrate SUB. The thin-film transistor layer TFTL may include a barrier layer BR, a thin-film transistor TFT1, a first capacitor electrode CAE1, a second capacitor electrode CAE2, a first anode connection electrode ANDE1, a second anode connection electrode ANDE2, a gate insulator **130**, a first interlayer dielectric film **141**, a second interlayer dielectric film **142**, a first planarization film **160**, a second planarization

film **180**.

[0071] The substrate SUB may be made of an insulating material such as a polymer resin. For example, the substrate SUB may be made of polyimide. The substrate SUB may be a flexible substrate that can be bent, folded, or rolled.

[0072] The barrier film BR may be disposed on the substrate SUB. The barrier film BR is a film for protecting the thin-film transistors of the thin-film transistor layer TFTL and an emissive layer **172** of the emission material layer EML. The barrier film BR may be made up of multiple inorganic films stacked on one another. For example, the barrier film BR may be made up of multiple layers in which one or more inorganic layers of a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer and an aluminum oxide layer are alternately stacked on one another.

[0073] The thin-film transistors TFT**1** may be disposed on the barrier film BR.

[0074] An active layer ACT**1** of the thin-film transistor TFT**1** may be disposed on the barrier layer BR. The active layer ACT**1** of the thin-film transistor TFT**1** may include, for example, polycrystalline silicon, monocrystalline silicon, low-temperature polycrystalline silicon, amorphous silicon, or an oxide semiconductor.

[0075] The active layer ACT**1** may include a channel region CHA**1**, a source region S**1** and a drain region D**1**. The channel region CHA**1** may overlap with a gate electrode G**1** in the third direction DR**3**, for example, the thickness direction of the substrate SUB. The source region S**1** may be disposed on one side of the channel region CHA**1**, and the drain region D**1** may be disposed on the opposite side of the channel region CHA**1**. The source region S**1** and the drain region D**1** might not overlap with the gate electrode G**1** in the third direction DR**3**. The source region S**1** and the drain region D**1** may be formed by doping a silicon semiconductor or an oxide semiconductor with ions or impurities to have conductivity.

[0076] The gate insulator **130** may be disposed on the active layer ACT**1** of the thin-film transistor TFT**1**. The gate insulator **130** may be formed of an inorganic layer, for example, a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer, or an aluminum oxide layer.

[0077] The gate electrode G**1** and the first capacitor electrode CAE**1** of the thin-film transistor TFT**1** may be disposed on the gate insulator **130**. The gate electrode G**1** may overlap with the active layer ACT**1** in the third direction DR**3**. Although the gate electrode G**1** and the first capacitor electrode CAE**1** are spaced apart from each other in the example shown in FIG. **5**, the gate electrode G**1** and the first capacitor electrode CAE**1** may be connected with each other as a single piece. For example, the gate electrode G**1** and the first capacitor electrode CAE**1** may be an integrated layer. The gate electrode G**1** and the first capacitor electrode CAE**1** may be made up of a single layer or multiple layers of one of molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0078] The first interlayer dielectric film **141** may be disposed on the gate electrode G**1** of the thin-film transistor TFT**1** and the first capacitor electrode CAE**1**. The first interlayer dielectric film **141** may be formed of an inorganic layer, for example, a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer, or an aluminum oxide layer. The first interlayer dielectric film **141** may be made of a plurality of inorganic films. However, the present invention is not limited thereto.

[0079] The second capacitor electrode CAE**2** may be disposed on the first interlayer dielectric layer **141**. The second capacitor electrode CAE**2** may overlap the first capacitor electrode CAE**1** of the thin-film transistor TFT**1** in the third direction DR**3**. In addition, when the gate electrode G**1** and the first capacitor electrode CAE**1** are formed as a single piece, the second capacitor electrode CAE**2** may overlap the gate electrode G**1** in the third direction DR**3**. Since the first interlayer dielectric layer **141** has a predetermined dielectric constant, a capacitor can be formed by the first capacitor electrode CAE**1**, the second capacitor electrode CAE**2** and the first interlayer dielectric

layer **141** disposed therebetween. The second capacitor electrode CAE2 may be made up of a single layer or multiple layers of one of, for example, molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0080] A second interlayer dielectric layer **142** may be disposed over the second capacitor electrode CAE2. The second interlayer dielectric film **142** may be formed of an inorganic layer, for example, a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer, or an aluminum oxide layer. The second interlayer dielectric film **142** may be made of a plurality of inorganic films. However, the present invention is not limited thereto.

[0081] A first anode connection electrode ANDE1 may be disposed on the second interlayer dielectric layer **142**. The first anode connection electrode ANDE1 may be connected to the drain electrode D1 of the thin-film transistor TFT1 through a first connection contact hole ANCT1 that penetrates the gate insulator **130**, the first interlayer dielectric film **141** and the second interlayer dielectric film **142**. The first anode connection electrode ANDE1 may be made up of a single layer or multiple layers of one of, for example, molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0082] A first planarization film **160** may be disposed over the first anode connection electrode ANDE1 and may provide a flat surface over level differences that are formed from the thin-film transistor TFT1. The first planarization film **160** may be formed of an organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0083] A second anode connection electrode ANDE2 may be disposed on the first planarization layer **160**. The second anode connection electrode ANDE2 may be connected to the first anode connection electrode ANDE1 through a second connection contact hole ANCT2 that penetrates the first planarization layer **160**. The second anode connection electrode ANDE2 may be made up of a single layer or multiple layers of one of, for example, molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0084] A second planarization film **180** may be disposed on the second anode connection electrode ANDE2. The second planarization film **180** may be formed as an organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0085] An emission material layer EML including light-emitting elements LEL and a bank **190** may be disposed on the second planarization film **180**. Each of the light-emitting elements LEL includes a pixel electrode **171**, an emissive layer **172**, and a common electrode **173**.

[0086] The pixel electrode **171** may be disposed on the second planarization film **180**. The pixel electrode **171** may be connected to the second anode connection electrode ANDE2 through a third connection contact hole ANCT3 that penetrates the second planarization film **180**.

[0087] In the top-emission structure in which light exits from the emissive layer **172** toward the common electrode **173**, the pixel electrode **171** may be made of a metal material having a high reflectivity such as a stack structure of aluminum and titanium (Ti/Al/Ti), a stack structure of aluminum (Al) and ITO (Indium Tin Oxide) (ITO/Al/ITO), an APC alloy and a stack structure of an APC alloy and ITO (ITO/APC/ITO). The APC alloy is an alloy of silver (Ag), palladium (Pd) and copper (Cu).

[0088] To define the first emission area, the second emission area EA2, the third emission area EA3 and the fourth emission area, the bank **190** may be formed to partition the pixel electrode **171** on the second planarization film **180**. The bank **190** may be disposed to cover the edges of the pixel electrode **171**. The bank **190** may be formed of an organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0089] In each of the first emission area, the second emission area EA2, the third emission area EA3 and the fourth emission area, the pixel electrode **171**, the emissive layer **172** and the common electrode **173** are stacked on one another sequentially, so that holes from the pixel electrode **171**

and electrons from the common electrode **173** are recombined with each other in the emissive layer **172** to emit light.

[0090] The emissive layer **172** may be disposed on the pixel electrode **171** and the bank **190**. The emissive layer **172** may include an organic material to emit light of a certain color. For example, the emissive layer **172** may include a hole transporting layer, an organic material layer, and an electron transporting layer.

[0091] The common electrode **173** may be disposed on the emissive layer **172** and the bank **190**. The common electrode **173** may be disposed to cover the emissive layer **172**. The common electrode **173** may be a common layer that is formed commonly in the first emission area, the second emission area EA2, the third emission area EA3 and the fourth emission area. A capping layer may be formed on the common electrode **173**.

[0092] In the top-emission organic light-emitting diode, the common electrode **173** may be formed of a transparent conductive material (TCP) such as ITO and IZO that can transmit light, or a semi-transmissive conductive material such as magnesium (Mg), silver (Ag) and an alloy of magnesium (Mg) and silver (Ag). When the common electrode **173** is formed of a semi-transmissive metal material, the light extraction efficiency can be increased by using microcavities.

[0093] A spacer **191** may be disposed on the bank **190**. The spacer **191** may support a mask during a process of fabricating the emissive layer **172**. The spacer **191** may be formed of an organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0094] An encapsulation layer TFEL may be disposed on the common electrode **173**. The encapsulation layer TFEL includes at least one inorganic film to prevent permeation of oxygen or moisture into the emission material layer EML. In addition, the encapsulation layer TFEL includes at least one organic layer to protect the light-emitting element layer EML from foreign substances such as dust. For example, the encapsulation layer TFEL includes a first inorganic encapsulation film TFE1, an organic encapsulation film TFE2 and a second inorganic encapsulation layer TFE3.

[0095] The first inorganic encapsulation film TFE1 may be disposed on the common electrode **173**. The organic encapsulation film TFE2 may be disposed on the first inorganic encapsulation film TFE1, and the second inorganic encapsulation film TFE3 may be disposed on the organic encapsulation film TFE2. For example, the first inorganic encapsulation film TFE1 and the second inorganic encapsulation film TFE3 may be made up of multiple layers in which one or more inorganic layers of a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer and an aluminum oxide layer are alternately stacked on one another. The organic encapsulation film TFE2 may be an organic film such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin, a polyimide resin, etc.

[0096] A touch detecting layer TDL may be disposed on the encapsulation layer TFEL. The touch detecting layer TDL includes a first touch insulating film TINS1, connection electrodes BE, a second touch insulating film TINS2, the driving electrodes TE, the sensing electrodes RE, and a third touch insulating film TINS3.

[0097] The first touch insulating film TINS1 may be disposed on the encapsulation layer TFEL. The first touch insulating film TINS1 may be formed of an inorganic layer, for example, a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer, or an aluminum oxide layer.

[0098] The connection electrode BE1 may be disposed on the first touch insulating film TINS1. The connection electrode BE1 may be made up of a single layer or multiple layers of one of, for example, molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0099] The second touch insulating film TINS2 is disposed over the connection electrodes BE1. The second touch insulating layer TINS2 may be formed of an inorganic layer, for example, a silicon nitride layer, a silicon oxynitride layer, a silicon oxide layer, a titanium oxide layer, or an aluminum oxide layer. In addition, the second touch insulating layer TINS2 may be formed of an

organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0100] The driving electrodes TE and the sensing electrodes RE may be disposed on the second touch insulating film TINS2. In addition to the driving electrodes TE and the sensing electrodes RE, the dummy patterns DE, the first touch driving lines, the second touch driving lines and the touch sensing lines may be disposed on the second touch insulating film TINS1. The driving electrodes TE and the sensing electrodes RE may be made up of a single layer or multiple layers of one of, for example, molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd) and copper (Cu) or an alloy thereof.

[0101] The driving electrodes TE and the sensing electrodes RE may overlap with the connection electrodes BE1 in the third direction DR3. The driving electrodes TE may be connected to the connection electrodes BE1 through touch contact holes TCNT1 that penetrate through the first touch insulating film TINS1.

[0102] The third touch insulating film TINS3 is formed over the driving electrodes TE and the sensing electrodes RE. The third touch insulating layer TINS3 may provide a flat surface over the driving electrodes TE, the sensing electrodes RE and the connection electrodes BE1 which having different heights. The third touch insulating film TINS3 may be formed of an organic layer such as an acryl resin, an epoxy resin, a phenolic resin, a polyamide resin and a polyimide resin.

[0103] FIG. 6 is an enlarged cross-sectional view of a patterned portion of FIGS. 3 and 4. FIG. 7 is an enlarged cross-sectional view of a part of the patterned portion of FIG. 6.

[0104] Referring to FIG. 6, the cover window 200 may include an upper surface 211, which is a first surface facing the upper protection member 100 of FIG. 3, and a lower surface 212, which is a second surface facing the display panel 400 having the first adhesive member 300 attached thereto as the opposite surface to the upper surface 211.

[0105] The cover window 200 may include the patterned portion 221 and 232 formed in the folding area FDA.

[0106] The patterned portion 221 and 232 may be formed in a part of the cover window 200 in the horizontal direction that has a width L that is substantially equal to the width of the folding area FDA. For example, the patterned portion 221 and 232 formed only in a part of the cover window 200 in FIGS. 3 and 4 may have the width L.

[0107] The patterned portion 221 and 232 may include a plurality of first concave grooves 221 and a plurality of second concave grooves 232, and the plurality of first concave grooves 221 and the plurality of second concave grooves 232 disposed in the folding area FDA.

[0108] The first concave grooves 221 may be formed in the upper surface 211 of the cover window 200, and the first concave grooves 221 may be spaced apart from one another along the horizontal direction, which is the surface direction of the upper surface 211.

[0109] For example, an odd number of first concave grooves 221 may be formed for symmetry when the cover window 200 is folded. The number of the first concave grooves 221 may be greater than the number of the second concave grooves 232.

[0110] The second concave grooves 232 may be formed in the lower surface 212 of the cover window 200, and the second concave grooves 232 may be spaced apart from one another along the horizontal direction, which is the surface direction of the upper surface 212. For example, the number of the second concave grooves 232 may be smaller than the number of the first concave grooves 221. However, the present invention is not limited thereto. For example, the number of the second concave grooves 232 may be larger than the number of the first concave grooves 221.

[0111] The first concave grooves 221 and the second concave grooves 232 may be arranged alternately so that they do not overlap each other.

[0112] Referring to FIG. 7, each of the first concave grooves 221 may be located in the upper surface 211 of the cover window 200 and may include a concave groove shape that is recessed toward the lower surface 212.

[0113] Each of the second concave grooves **232** may be located in the lower surface **212** of the cover window **200** and may include a concave groove shape that is recessed toward the upper surface **212**.

[0114] The first concave grooves **221** may have, but is not limited to, a semicircular cross-sectional shape or a polygonal cross-sectional shape. They may be formed in a variety of shapes.

[0115] The second concave grooves **232** may have, but is not limited to, a semicircular cross-sectional shape or a polygonal cross-sectional shape, like the first concave grooves **221**. The second concave grooves **232** may be arranged alternately with the first concave grooves **221** and may have a different shape from that of the first concave grooves **221**. However, the present invention is not limited thereto. For example, the second concave grooves **232** may be alternately arranged with different shapes from each other.

[0116] FIG. **8** is an enlarged cross-sectional view of the first and second concave grooves of FIG. **7**. FIG. **9** is a view showing the folding state of the cover glass when it is folded together with the display panel.

[0117] Referring to FIG. **8**, since the first concave grooves **221** and the second concave grooves **232** have the same shape and the same configuration as each other, except for being formed in different surfaces of the cover window **200**, the following description will be made based on the first concave grooves **221**.

[0118] The first concave groove **221** may be formed in the upper surface **211** of the cover window **200**. The first concave groove **221** may include inner walls **223**, curved surfaces **224**, and an opening **222**. The inner walls **223** may extend from the upper surface **211** of the cover window **200**. The curved surfaces **224** may extend from the inner walls **223**, and the opening **222** may expose the curved surfaces **224** on the opposite side of the curved surfaces **224**.

[0119] The inner walls **223** refer to the both inner side surfaces that are located in the internal space of the first concave groove **221** and may be located between a first line **L1** and a second line **L2**, which are straight lines in a cross section.

[0120] The curved surfaces **224** may be internal bottom surfaces that are located in the internal space of the first concave groove **221**, and may have a semicircular shape forming a curve in a cross section.

[0121] For example, the curved surfaces **224** may be in the form of a parabola having a vertex where a third line **L3**, which is the horizontal line passing through the end (e.g., the lowest point) of the first concave groove **221**, and a fourth line **L4**, which is a vertical line, intersect each other. For example, the fourth line **L4** is a vertical line that extends through a center of the first concave groove **221**.

[0122] An angle θ formed by the inner wall **223** of the first concave groove and the upper surface **211** of the cover window **200** may range from about 80 degrees to about 89 degrees.

[0123] For example, the angle θ formed by the first line **L1**, which is a straight line extending parallel to the upper surface **211** of the cover window **200**, and the inner wall **223** may range from about 80 degrees to about 89 degrees, for example, about 84 degrees to about 88 degrees.

[0124] The first concave groove **221** may have a curvature radius r that is greater than about 10 μm and less than about 30 μm . For example, the first concave groove **221** may have a curvature radius r that is about 20 μm at a vertex **A**, which is the end of the first concave groove **221**.

[0125] The curvature radius r at the vertex **A** of the first concave groove **221** may be smaller than the radius of curvature at the boundary between the inner wall **223** and the curved surface **224** of the first concave groove **221**.

[0126] That is to say, in the first concave groove **221**, the curvature radius r of a circle drawn at the vertex **A** may be smaller than the radius of curvature of a circle drawn with the center at the intersection point where the second line **L2** and the fourth line **LA** intersect each other.

[0127] Herein, the second concave groove **232** is identical to the above-described first concave groove **221**, and the angle θ and the radius of curvature r of the second concave groove **232** may

be equal to those of the first concave groove **221**.

[0128] In the patterned portion **221** and **232** including the first concave groove **221** and the second concave groove **232** as described above, the width L of the patterned portion shown in FIGS. **3**, **4** and **6** may satisfy the mathematical expression that is below. That is to say, the width L of the patterned portion can be formed in a numerical range that satisfies the mathematical expression below:

$L \leq (r+T)+1$ [Mathematical Expression]

where r denotes the radius of curvature (r) of the cover window **200** that is folded together with the display panel **400**, which is the curvature radius (r) of the cover window shown in FIG. **9**. T denotes the thickness of the cover window **200**, and L denotes the width of the patterned portion **221** and **232** including the plurality of first and second concave grooves **221** and **232**.

[0129] As an example, the radius of curvature r of the cover window in FIG. **9** is 1.19 mm, and the thickness T of the cover window in FIG. **8** is 150 μm or 0.15 mm. By inputting the values to the mathematical expression, the calculated value of L is 5.20 mm. The value was calculated to two decimal places.

[0130] When the calculated width L of the patterned portion **221** and **232** is 5.20 mm, to form the patterned portion **221** and **232** including a plurality of first and second concave grooves **221** and **232**, the patterned portion **221** and **232** may be formed with the width of 5.20 mm at a central part of the cover window **200** in the horizontal direction shown in FIGS. **3** and **4**. That is to say, a plurality of first and second concave grooves **221** and **232** may be formed along the horizontal direction as wide as the L value of 5.20 mm.

[0131] The L value, which is the width of the patterned portion, may be greater than about 4 mm and smaller than about 5.5 mm, For example, the L value may be about 5.2 mm.

[0132] FIG. **10** is a view showing stress and strain test results according to the width L of the patterned portion of the cover window.

[0133] Referring to FIG. **10**, results of tests T**1** to T**4** are shown. For tests T**1** to T**3**, if the width L is greater than about 4 mm and less than about 5.5 mm, the patterned portion can be normally folded without deviating from the dotted line, which is the reference line, that is, without reverse bending that deviates from the dotted line. In addition, it can be seen that the stress and strain values do not increase significantly.

[0134] However, when the width L exceeds about 5.3 mm, i.e., in test T**4**, while the stress value is lower than in tests T**1** to T**3**, reverse bending beyond the dotted line occurs as shown in FIG. **10**. It can be seen from FIG. **10** that the stress and strain values do not increase significantly while the patterned portion can be folded normally and most stably when the L value is 5.2 mm in test T**3**.

[0135] FIG. **11** is a view showing test results according to the radius of curvature Ir of the concave groove of FIG. **8**.

[0136] Referring to FIG. **11**, results of testing the stress and strain in test T**5** with the radius of curvature Ir of about 10 μm and test T**6** with the radius of curvature Ir of about 20 μm are shown. It can be seen from FIG. **11** that the patterned portion can be normally folded in tests T**5** and T**6** even when stress is applied if a normal pattern is formed. It should be noted that in test T**6** where the radius of curvature is about 20 μm greater than about 10 μm , it can be seen that the stress and strain values greatly decrease. In view of the above, it can be seen that the most desirable value of the radius of curvature of the concave groove Ir is about 20 μm .

[0137] As described above, to form the first and second concave grooves **221** and **232**, the angle θ of the groove is formed from about 84 degrees to about 88 degrees, the radius of curvature Ir of the concave groove is greater than about 10 μm and less than about 20 μm , and the patterned portion **221** and **232** including the first and second concave grooves **221** and **232** have the width L that satisfies the mathematical expression $L \leq (r+T)+1$. By doing so, the patterned portion of the cover window **200** can be folded normally so that it is horizontally symmetrical as shown in FIG. **9**, and

the impact resistance can be increased and increased flexibility can be provided, which are desirable characteristics for the foldable display device **10** as shown in FIGS. **10** and **11**.

[0138] In addition, to increase the impact resistance and provide the flexibility of the foldable display device **10**, the width **L** of the patterned portion **221** and **232** is determined based on the mathematical expression, so that it is possible to prevent defects such as buckling as well as increasing impact resistance and providing excellent flexibility, which are desirable characteristics for foldable display devices.

[0139] In addition, it is possible to provide repeatability that allows the patterns of the first and second concave grooves **221** and **232** to be formed consistently and repeatedly at constant intervals.

[0140] If the radius of curvature **r** of the cover window is set but the width **L** of the patterned portion is not set by the mathematical expression, reverse bending may occur that deviates from the dotted line, which is the reference line, as in test **T4** of FIG. **10**. As a result, the cover window **200** may be damaged.

[0141] FIG. **12** is a view showing chamfered surfaces formed in the first and second concave grooves of FIG. **8**.

[0142] Referring to FIG. **12**, a cover window **200a** according to an embodiment of the present invention may include chamfered surfaces between inner walls **223** of the first and second concave grooves **221** and **232** and the upper surface **211** of the cover window **200**. The cover window **200a** according to this embodiment is substantially identical to the cover window **200** of FIG. **8** except for the chamfered surfaces **420**, and, therefore, the redundant descriptions will be omitted or briefly discussed.

[0143] The chamfered surface **240** may be formed by chamfering a corner of the cover window **200a** in the direction of the arrow.

[0144] The minimum length of the chamfered surface **240** from the inner wall of the first concave groove **221** to the upper surface **211** of the cover window **200** may range from about 2 μm to about 10 μm . For example, in a triangle formed by dotted lines with the chamfer surface **240** as the base, the length **W** of the both isosceles sides may range from about 2 μm to 10 μm .

[0145] By forming the chamfer surface **240**, stress is concentrated in the corner area generated when the first and second concave grooves **221** and **232** are formed, thereby preventing the risk of breakage and increasing rigidity.

[0146] FIG. **13** is a view showing the test results of impact resistance of the chamfered surface of FIG. **12**.

[0147] Referring to FIG. **13**, a chamfered surface **240** was formed adjacent to first and second concave grooves **221** and **232**, and then, a pen drop test was conducted for testing impact resistance. It can be seen that when the chamfered surface **240** is formed on both the upper surface **211** and the lower surface **212** of the cover window **200a**, the impact resistance performance is increased. For example, when the chamfered surface **240** is formed in the lower surface **212**, it was checked that breakage occurs only when the pen is dropped from a height of up to about 16 cm, 19 cm, and 21 cm. In view of the above, it can be seen that the impact resistance is increased when the chamfer surface **240** is formed in the lower surface **212** than when the chamfered surface **240** is formed in the upper surface **211**.

[0148] Hereinafter, a method for fabricating a display device according to an embodiment of the present invention will be described with reference to FIG. **14**.

[0149] FIG. **14** is a flowchart for illustrating a method for fabricating a display device according to an embodiment of the present invention.

[0150] First, the method may include preparing a cover window **200** to protect a display panel **400** (step **S110** in FIG. **14**).

[0151] The preparing the cover window **200** may include disposing a cover window on the display panel **400** including a folding area **FDA**, a first non-folding area **NFA1** disposed on one side of the folding area **FDA** and a second non-folding area **NFA2** on the opposite side of the folding area

FDA.

[0152] In doing so, the width L of the patterned portion **221** and **232** of the cover window **200** may be located in line with the folding area FDA.

[0153] Second, the method may include forming first concave grooves **221** in an upper surface **211** of the cover window **200** (step **S120** in FIG. **14**).

[0154] In doing so, a plurality of first concave grooves **221** may be formed with a semicircular cross-sectional shape along the surface direction of the upper surface **211** of the cover window **200**. For example, an odd number of first concave grooves **221** may be formed, and the number of first concave grooves **221** may be greater than that of the plurality of second concave grooves **232**.

[0155] Third, the method may include forming a plurality of second concave grooves **232** in a lower surface **212** of the cover window **200** (step **S130** in FIG. **14**).

[0156] In doing so, a plurality of second concave grooves **232** may be formed with a semicircular cross-sectional shape along the surface direction of the lower surface **212** of the cover window **200**, and the first concave grooves **221** and the second concave grooves **232** may be alternately arranged with each other. For example, the number of the second concave grooves **232** may be less than the number of the first concave grooves **221** by one.

[0157] The order of forming the first and second concave grooves **221** and **232** is not limited to steps **S120** and **S130**. The second concave grooves **232** may be formed first, and then, the first concave grooves **221** may be formed.

[0158] In steps **S120** and **130**, the first and second concave grooves **221** and **232** may be commonly formed by using a laser-induced deep etching (LIDE).

[0159] As a method of forming concave grooves such as the first and second concave grooves **221** and **232**, the LIDE may include irradiating the cover window **200** with laser and etching the irradiated area. The etching step may be wet etching as chemical etching.

[0160] In addition, in steps **S120** and **130**, to form the first and second concave grooves **221** and **232**, the angle θ of the grooves may be formed from about 84 degrees to about 88 degrees, the radius of curvature I_r of the concave grooves may be greater than about 10 μm and less than about 20 μm , and the patterned portion **221** and **232** including the first and second concave grooves **221** and **232** may have the width L that satisfies the mathematical expression $L \leq \pi(r+T)+1$.

[0161] The method may further include forming a chamfered surface **240** subsequent to steps **S120** and **S130**.

[0162] The chamfered surface **240** may be formed by cutting off a corner area of the cover window **200a** to a length W that is about 2 μm to 10 μm in an opening **222** of the cover window **200a**.

[0163] As described above, to form the first and second concave grooves **221** and **232**, the angle θ of the groove is formed from about 84 degrees to about 88 degrees, the radius of curvature I_r of the concave groove is greater than about 10 μm and less than about 20 μm , and the patterned portion **221** and **232** including the first and second concave grooves **221** and **232** have the width L that satisfies the mathematical expression $L \leq (r+T)+1$. In doing so, the L value is formed greater than about 4 mm and less than about 5.5 mm, and the chamfered surface has a size of about 2 μm to 10 μm , for example, so that the impact resistance can be increased and increased flexibility can be provided, which are desirable characteristics for the foldable display devices.

[0164] In addition, by providing increased flexibility when the device is folded, it is possible to suppress abnormal folding, reverse bending, etc., and, accordingly, to prevent defects such as damage to the cover window.

[0165] In addition, the same pattern can be repeatedly formed with a constant interval by using the reference value as described above, so that it is possible to provide repeatability in pattern formation.

[0166] While the present invention has been described with reference to the embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and detail may be made thereto without departing from the spirit and scope of the present invention.

Claims

1. A display device comprising: a display panel comprising a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on second side of the folding area; and a cover window located on the display panel and having a patterned portion formed to overlap the folding area, wherein the patterned portion comprises a plurality of first concave grooves and a plurality of second concave grooves, wherein the plurality of first concave grooves are formed in a first surface of the cover window, and the plurality of second concave grooves are formed in a second surface of the cover window that is opposite to the first surface and faces the display panel, wherein each of the plurality of first and second concave grooves comprises an inner wall that extends from the first surface or the second surface of the cover window and a curved surface that extends from the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm , and wherein the patterned portion has a width in a first direction of the cover window, wherein the width is calculated by a following equation:
$$L \leq (r + T) + 1$$
 wherein r denotes a radius of curvature of the cover window disposed at a position overlapping with the folding area when the display panel is folded, wherein T denotes a thickness of the cover window, and L denotes the width of the patterned portion.
2. The display device of claim 1, wherein the radius of curvature at the end of the curved surface is smaller than the radius of curvature of the curved surface at a boundary between the inner wall and the curved surface.
3. The display device of claim 2, wherein the first concave groove further comprises a chamfered surface that is disposed between the inner wall of the first concave groove and the first surface of the cover window.
4. The display device of claim 3, wherein a minimum length of the chamfered surface from the inner wall of the first concave groove to the first surface of the cover window ranges from about 2 μm to 10 μm .
5. The display device of claim 4, wherein an angle formed by the first surface of the cover window and the chamfered surface is smaller than an angle that is formed by the first surface of the cover window and the inner wall of the first concave groove.
6. The display device of claim 5, wherein the plurality of first concave grooves and the plurality of second concave grooves have a same shape as each other, wherein the first concave grooves are recessed from the first surface toward the second surface, and wherein the second concave grooves are recessed from the second surface toward the first surface.
7. The display device of claim 6, wherein the first concave grooves and the second concave grooves are alternately arranged with each other.
8. The display device of claim 7, wherein each of the first concave grooves and the second concave grooves has a semicircular shape or a polygonal shape.
9. The display device of claim 6, wherein a number of the first concave grooves is greater than a number of the second concave grooves.
10. The display device of claim 9, wherein the number of the first concave grooves is odd.
11. A display device comprising: a display panel comprising a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on a second side of the folding area; and a cover window located on the display panel and having a pattern portion overlapping the folding area, wherein the pattern portion comprises a plurality of first concave grooves and a plurality of second concave grooves, wherein the plurality of first concave grooves are formed in a first surface of the cover window, and the plurality of second concave grooves are

formed in a second surface of the cover window opposite to the first surface and facing the display panel, wherein each of the plurality of first and second concave grooves comprises an inner wall that extends from the first surface or the second surface of the cover window, a curved surface that extends from the inner wall, and a chamfered surface located adjacent to the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, and wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm .

12. The display device of claim 11, wherein a minimum length of the chamfered surface from the inner wall to the first surface of the cover window ranges from about 2 μm to 10 μm .

13. The display device of claim 12, wherein an angle formed by the first surface of the cover window and the chamfered surface is smaller than an angle that is formed by the first surface of the cover window and the inner wall of the first concave groove.

14. The display device of claim 11, wherein the radius of curvature at the end of the curved surface is smaller than the radius of curvature of the curved surface at a boundary between the inner wall and the curved surface.

15. The display device of claim 11, wherein the plurality of first concave grooves and the plurality of second concave grooves have a same shape as each other, wherein the first concave grooves are recessed from the first surface toward the second surface, and wherein the second concave grooves are recessed from the second surface toward the first surface.

16. The display device of claim 15, wherein the first concave grooves and the second concave grooves are alternately arranged with each other.

17. The display device of claim 16, wherein a number of the first concave grooves is greater than a number of the second concave grooves.

18. A method for fabricating a display device, the method comprising: preparing a cover window for protecting a display panel comprising a folding area, a first non-folding area disposed on a first side of the folding area, and a second non-folding area disposed on a second side of the folding area; and forming a patterned portion in the cover window to overlap with the folding area, wherein the forming of the patterned portion in the cover window comprises: forming a plurality of first concave grooves in a first surface of the cover window; and forming a plurality of second concave grooves in a second surface of the cover window that is opposite to the first surface, wherein each of the plurality of first and second concave grooves comprises an inner wall that extends from the first surface or the second surface of the cover window and a curved surface that extends from the inner wall, wherein an angle formed by the first surface of the cover window and the inner wall of the first concave groove ranges from about 80 degrees to about 89 degrees, wherein a radius of curvature at an end of the curved surface of the first concave groove is greater than about 10 μm and less than about 30 μm , and wherein the patterned portion has a width in a first direction of the cover window, wherein the width is calculated by a following equation:

$L \leq (r+T)+1$, wherein r denotes a radius of curvature of the cover window disposed at a position overlapping with the folding area when the display panel is folded, wherein T denotes a thickness of the cover window, and L denotes the width of the patterned portion.

19. The method of claim 18, further comprising: forming a chamfered surface in each of the first and second concave grooves by chamfering.

20. The method of claim 18, wherein the first and second concave grooves are formed by laser-induced deep etching (LIDE).
