

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402370
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Kim; Guk Hwan

Semiconductor device and manufacturing method of semiconductor device

Abstract

A semiconductor device includes a source region, a drain region, and a gate insulating film formed on a substrate, a gate electrode formed on the gate insulating film, a first insulating film pattern formed to extend from the source region to a part of a top surface of the gate electrode, and a spacer formed on a side surface of the gate electrode in a direction of the drain region.

Inventors:	Kim; Guk Hwan (Cheongju-si, KR)
Applicant:	MagnaChip Semiconductor, Ltd. (Cheongju-si, KR)
Family ID:	1000008778706
Assignee:	MagnaChip Semiconductor, Ltd. (Cheongju-si, KR)
Appl. No.:	17/940461
Filed:	September 08, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230006039 A1	Jan. 05, 2023

Foreign Application Priority Data

KR	10-2020-0040312	Apr. 02, 2020
----	-----------------	---------------

Related U.S. Application Data

continuation parent-doc US 17844344 20220620 US 11996444 child-doc US 17940461
division parent-doc US 16928307 20200714 US 11430863 20220830 child-doc US 17844344

Publication Classification

Int. Cl.: **H10D64/01** (20250101); **H10D62/10** (20250101); **H10D64/23** (20250101); **H10D64/27** (20250101); **H10D89/60** (20250101)

U.S. Cl.:

CPC **H10D62/112** (20250101); **H10D64/01** (20250101); **H10D64/258** (20250101); **H10D64/514** (20250101); **H10D89/601** (20250101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8338281	12/2011	Choi et al.	N/A	N/A
9871063	12/2017	Oh et al.	N/A	N/A
10566422	12/2019	Lee et al.	N/A	N/A
10727300	12/2019	Kim et al.	N/A	N/A
2008/0179639	12/2007	Gambino	438/57	H01L 27/14603
2009/0166765	12/2008	Lee	N/A	N/A
2011/0042756	12/2010	Hikida	N/A	N/A
2012/0228704	12/2011	Ju	257/E29.256	H01L 29/66689
2013/0020632	12/2012	Disney	257/E21.409	H01L 29/0847
2013/0134512	12/2012	Cheng	257/E29.256	H01L 29/402
2013/0299919	12/2012	Chen et al.	N/A	N/A
2015/0102405	12/2014	Ryu et al.	N/A	N/A
2016/0190269	12/2015	Brown	438/286	H10D 30/0221
2016/0204279	12/2015	Horch et al.	N/A	N/A
2017/0352731	12/2016	Kuo	N/A	H10D 30/0212
2018/0019262	12/2017	Oh et al.	N/A	N/A
2018/0097065	12/2017	Zhu	N/A	H10D 30/025
2018/0358349	12/2017	Hwang et al.	N/A	N/A
2019/0019866	12/2018	Kim	N/A	H10D 64/516
2019/0221666	12/2018	Bang	N/A	H10D 64/62
2019/0288066	12/2018	Lee	N/A	H10D 30/0221
2020/0251575	12/2019	Kim et al.	N/A	N/A
2020/0279925	12/2019	Fan et al.	N/A	N/A
2020/0357887	12/2019	Chabak et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
10 2008 063 324	12/2008	DE	N/A
9-82949	12/1996	JP	N/A
10-2009-0073487	12/2008	KR	N/A
10-2010-0079175	12/2009	KR	N/A
10-2018-0009009	12/2017	KR	N/A
10-2019-0008463	12/2018	KR	N/A
10-2019-0109685	12/2018	KR	N/A
10-2020-0008170	12/2019	KR	N/A
10-2020-0095640	12/2019	KR	N/A

OTHER PUBLICATIONS

German Office Action issued on Jun. 12, 2023, in corresponding German Patent Application No. 102020124781.8 (12 pages in English, 12 pages in German). cited by applicant

Korean Office Action issued on Oct. 9, 2021 in counterpart Korean Patent Application No. 10-2020-0100930 (13 pages in Korean). cited by applicant

Korean Office Action Issued on Apr. 23, 2021 in counterpart Korean Patent Application No. 10-2020-0040312 (8 pages in Korean). cited by applicant

Korean Office Action issued on Aug. 12, 2021 in counterpart Korean Patent Application No. 10-2020-0040312 (7 pages in Korean). cited by applicant

Primary Examiner: Jahan; Bilkis

Attorney, Agent or Firm: NSIP Law

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 17/844,344, filed on Jun. 20, 2022, which is a divisional application of U.S. patent application Ser. No. 16/928,307, filed on Jul. 14, 2020, which claims the benefit under 35 U.S.C. 119(a) of Korean Patent Application No. 10-2020-0040312 filed on Apr. 2, 2020 in the Korean Intellectual Property Office, the entire disclosure of which is incorporated herein by reference for all purposes.

BACKGROUND

1. Field

(1) The following description relates to a semiconductor device. The following description also relates to a method of manufacturing such a semiconductor device.

2. Description of Related Art

(2) In general, an ESD circuit may be formed to protect a semiconductor device formed inside a core circuit from an electrostatic discharge (ESD) or an electrical over stress (EOS). In addition, a gate insulating film may be formed to be thick in order to be prepared for an example in which an ESD or an EOS enters through the gate electrode of the semiconductor device. Such an approach may be used because a thin gate insulating film may be destroyed when an ESD or an EOS is applied to the semiconductor device. In addition, in order to withstand the ESD or the EOS, a structure in which the resistance of the gate electrode is increased may often be used. Therefore, in order to increase the resistance of the gate electrode, a silicide blocking insulating film may be

formed on the surface of the gate electrode. In this manner, a high ESD or a high EOS applied to the gate electrode may be mitigated to some extent.

(3) However, when a high electric field, such as an ESD or an EOS, is formed, there may take place a phenomenon in which leakage current occurs between the gate electrode and the drain electrode, or leakage current may occur between the gate electrode and source electrode. In order to prevent this phenomenon, the distance between the gate electrode and the drain electrode may be increased. Thus, despite a high electric field due to the ESD or the EOS, a leakage current between the gate electrode and the drain electrode may nonetheless be blocked. However, the source region and the gate electrode may be disposed to be as close as possible, in order to form a channel between the gate electrode and the source electrode. Due to using this structure, when a high electric field is applied to the gate electrode, a leakage current may occur between the gate electrode and the source electrode region.

SUMMARY

(4) This Summary is provided to introduce a selection of concepts in a simplified form that are further described below in the Detailed Description. This Summary is not intended to identify key features or essential features of the claimed subject matter, nor is it intended to be used as an aid in determining the scope of the claimed subject matter.

(5) In one general aspect, a semiconductor device includes a source region, a drain region, and a gate insulating film formed on a substrate, a gate electrode formed on the gate insulating film, a first insulating film pattern formed to extend from the source region to a part of a top surface of the gate electrode, and a spacer formed on a side surface of the gate electrode in a direction of the drain region.

(6) The semiconductor device may further include a second insulating film pattern formed to extend onto the gate electrode, the spacer, and the drain region.

(7) The first insulating film pattern and the second insulating film pattern may be in contact with each other.

(8) The second insulating film pattern may be thicker than the first insulating film pattern.

(9) The first insulating film pattern and the second insulating film pattern may be formed to be spaced apart from each other.

(10) The semiconductor device may further include a source silicide layer formed on the source region, a source contact plug formed on the source silicide layer, a drain silicide layer formed on the drain region, a drain contact plug formed on the drain silicide layer, a gate silicide layer formed on the gate electrode, and a gate contact plug formed on the gate silicide layer.

(11) The first insulating film pattern may partially overlap the source region and may contact the source silicide layer, and may be disposed to be spaced apart by a predetermined distance from the source contact plug.

(12) The second insulating film pattern may partially overlap the drain region, may contact the drain silicide layer, and may be disposed to be spaced apart by a predetermined distance from the drain contact plug.

(13) The first and second insulating film patterns may be formed to be spaced apart by a predetermined distance from the gate contact plug.

(14) The gate contact plug may be completely surrounded by the first insulating film pattern and the second insulating film pattern, when viewed from a top view of the semiconductor device.

(15) The semiconductor device may further include a first conductivity type well region formed on the substrate, a second conductivity type extended drain junction region formed to surround the drain region, a first conductivity type body region surrounding the source region, a first conductivity type body pickup region formed in the first conductivity type body region, a second conductivity type deep well region including the first conductivity type well region, and a second conductivity type deep well pickup region formed in the second conductivity type deep well region.

(16) The second insulating film pattern may be formed to directly contact the second conductivity

type extended drain junction region, the drain region, and the drain silicide layer.

(17) The first insulating film pattern may be formed to directly contact the first conductivity type body region, the source region, and the source silicide layer.

(18) The second insulating film pattern may have a third region formed on the substrate and a fourth region formed on the gate electrode, and a length of the third region may be shorter than a length of the fourth region.

(19) The top surface of the gate electrode may be formed to be in direct contact with the first insulating film pattern and the second insulating film pattern.

(20) The gate insulating film may include a first gate insulating film and a second gate insulating film having different thicknesses from each other.

(21) The first insulating film pattern may have a first region formed on the substrate and a second region formed on the gate electrode, and a length of the first region may be longer than a length of the second region.

(22) In another general aspect, a manufacturing method of a semiconductor device includes forming a gate insulating film and a gate electrode on a substrate, forming a first insulating film on an entire region of the substrate, forming a first mask pattern on the first insulating film, forming a first insulating film pattern on one end of the gate electrode using the first mask pattern, and forming a spacer on an other end of the gate electrode, removing the first mask pattern, forming a source region adjacent to the one end of the gate electrode, and forming a drain region adjacent to the other end of the gate electrode.

(23) The method may further include depositing a second insulating film on an entire surface of the substrate, forming a second mask pattern on the second insulating film, removing the second insulating film formed on the one end of the gate electrode by using the second mask pattern, and forming a second insulating film pattern on the other end of the gate electrode and the spacer; and removing the second mask pattern.

(24) The method may further include forming a drain silicide layer on the drain region, forming a source silicide layer on the source region, forming a gate silicide layer on the gate electrode, and forming a drain contact plug, a source contact plug, and a gate contact plug on the drain silicide layer, the source silicide layer, and the gate silicide layer, respectively.

(25) The method may further include forming a deep well region and a device isolation region on the substrate, forming a first conductivity type well region in the deep well region, forming a first conductivity type body region and a second conductivity type extended drain region on the first conductivity type well region, and forming a deep well pickup region and a body pickup region in the deep well region and the first conductivity type body region, respectively.

(26) The first insulating film pattern and the second insulating film pattern may be in contact with each other.

(27) The first insulating film pattern and the second insulating film pattern may be formed to be spaced apart from each other.

(28) The second insulating film pattern may be formed so as to overlap with the first insulating film pattern, and the second insulating film pattern may be formed on the first insulating film pattern.

(29) A thickness of the first insulating film pattern may be thinner than a thickness of the second insulating film pattern.

(30) The first insulating film pattern may partially overlap the source region and may contact the source silicide layer, and may be disposed spaced apart from the source contact plug by a predetermined distance.

(31) The second insulating film pattern may partially overlap the drain region, may contact the drain silicide layer, and may be disposed spaced apart from the drain contact plug by a predetermined distance.

(32) The first and second insulating film patterns may be formed spaced apart by a predetermined distance from the gate contact plug.

- (33) The first insulating film pattern may be formed to directly contact the first conductivity type body region, the source region, and the source silicide layer.
- (34) The second insulating film pattern may be formed to be in direct contact with the second conductivity type extended drain junction region, the drain region, and the drain silicide layer.
- (35) The method may further include forming a borderless contact insulating film and an interlayer insulating film on the drain silicide layer and the source silicide layer, forming the drain contact plug and the source contact plug, after the forming the borderless contact insulating film and an interlayer insulating film on the drain silicide layer and the source silicide layer.
- (36) The gate contact plug may be completely surrounded by the first insulating film pattern and the second insulating film pattern, when viewed from a top view of the semiconductor device.
- (37) A top surface of the gate electrode may be formed to be in direct contact with the first insulating film pattern and the second insulating film pattern.
- (38) In another general aspect, a semiconductor device includes a source region, a drain region, and a gate insulating film formed on a substrate, a gate electrode formed on the gate insulating film, a first insulating film pattern formed to extend from the source region to a part of the top surface of the gate electrode, and a second insulating film pattern formed to extend onto the gate electrode and the drain region.
- (39) The semiconductor device may further include a spacer formed on a side surface of the gate electrode in the direction of the drain region.
- (40) The second insulating film pattern may extend onto the spacer.
- (41) The first insulating film pattern and the second insulating film pattern may be in contact with each other.
- (42) The second insulating film pattern may be thicker than the first insulating film pattern.
- (43) The first insulating film pattern and the second insulating film pattern may be formed to be spaced apart from each other.
- (44) Other features and aspects will be apparent from the following detailed description, the drawings, and the claims.
-

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIGS. 1A and 1B are plan views of a semiconductor device, according to one or more examples.
- (2) FIGS. 2A, 2B, and 2C are cross-sectional views of a semiconductor device with respect to the line A-A' of FIG. 1.
- (3) FIGS. 3A, 3B, and 3C are cross-sectional views of a semiconductor device with respect to lines B-B' and C-C' of FIG. 1B.
- (4) FIGS. 4 to 8 are plan views of a semiconductor device, according to one or more examples.
- (5) FIGS. 9A to 9K are process diagrams illustrating a manufacturing process of a semiconductor device, according to one or more examples.
- (6) Throughout the drawings and the detailed description, the same reference numerals refer to the same elements. The drawings may not be to scale, and the relative size, proportions, and depiction of elements in the drawings may be exaggerated for clarity, illustration, and convenience.

DETAILED DESCRIPTION

- (7) The following detailed description is provided to assist the reader in gaining a comprehensive understanding of the methods, apparatuses, and/or systems described herein. However, various changes, modifications, and equivalents of the methods, apparatuses, and/or systems described herein will be apparent after an understanding of the disclosure of this application. For example, the sequences of operations described herein are merely examples, and are not limited to those set

forth herein, but may be changed as will be apparent after an understanding of the disclosure of this application, with the exception of operations necessarily occurring in a certain order. Also, descriptions of features that are known in the art may be omitted for increased clarity and conciseness.

(8) The features described herein may be embodied in different forms, and are not to be construed as being limited to the examples described herein. Rather, the examples described herein have been provided merely to illustrate some of the many possible ways of implementing the methods, apparatuses, and/or systems described herein that will be apparent after an understanding of the disclosure of this application.

(9) Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

(10) Throughout the specification, when an element, such as a layer, region, or substrate, is described as being “on,” “connected to,” or “coupled to” another element, it may be directly “on,” “connected to,” or “coupled to” the other element, or there may be one or more other elements intervening therebetween. In contrast, when an element is described as being “directly on,” “directly connected to,” or “directly coupled to” another element, there can be no other elements intervening therebetween.

(11) Although terms such as “first,” “second,” and “third” may be used herein to describe various members, components, regions, layers, or sections, these members, components, regions, layers, or sections are not to be limited by these terms. Rather, these terms are only used to distinguish one member, component, region, layer, or section from another member, component, region, layer, or section. Thus, a first member, component, region, layer, or section referred to in examples described herein may also be referred to as a second member, component, region, layer, or section without departing from the teachings of the examples.

(12) Spatially relative terms such as “above,” “upper,” “below,” and “lower” may be used herein for ease of description to describe one element's relationship to another element as shown in the figures. Such spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, an element described as being “above” or “upper” relative to another element will then be “below” or “lower” relative to the other element. Thus, the term “above” encompasses both the above and below orientations depending on the spatial orientation of the device. The device may also be oriented in other ways (for example, rotated 90 degrees or at other orientations), and the spatially relative terms used herein are to be interpreted accordingly.

(13) The terminology used herein is for describing various examples only, and is not to be used to limit the disclosure. The articles “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. The terms “comprises,” “includes,” and “has” specify the presence of stated features, numbers, operations, members, elements, and/or combinations thereof, but do not preclude the presence or addition of one or more other features, numbers, operations, members, elements, and/or combinations thereof.

(14) Due to manufacturing techniques and/or tolerances, variations of the shapes shown in the drawings may occur. Thus, the examples described herein are not limited to the specific shapes shown in the drawings, but include changes in shape that occur during manufacturing.

(15) The features of the examples described herein may be combined in various ways as will be apparent after an understanding of the disclosure of this application. Further, although the examples

described herein have a variety of configurations, other configurations are possible as will be apparent after an understanding of the disclosure of this application.

(16) Unless otherwise defined, all terms, including technical and scientific terms, used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure pertains and based on an understanding of the disclosure of the present application. Terms, such as those defined in commonly used dictionaries, are to be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the disclosure of the present application, and are not to be interpreted in an idealized or overly formal sense unless expressly so defined herein.

(17) Terms such as “including” or “comprising” used in the embodiments should not be construed as necessarily including all of various components, or various operations described in the specification, and it should be construed that some of the components or some of the operations may not be included or may further include additional components or operations.

(18) The use of the term “may” herein with respect to an example or embodiment (e.g., as to what an example or embodiment may include or implement) means that at least one example or embodiment exists where such a feature is included or implemented, while all examples are not limited thereto.

(19) Expressions such as “first conductivity type” and “second conductivity type” as used herein may refer to opposite conductivity types such as N and P conductivity types, and examples described herein using such expressions encompass complementary examples as well. For example, an example in which a first conductivity type is N and a second conductivity type is P encompasses an example in which the first conductivity type is P and the second conductivity type is N.

(20) The following description also provides a semiconductor device that may be capable of reducing leakage current, by increasing resistance between a gate electrode and a source region, and a manufacturing method of such a semiconductor device.

(21) FIG. 1A is a plan view of a semiconductor device, according to one or more examples, and FIG. 1B illustrates lines A-A', B-B', and C-C' in the plan view of FIG. 1A. Descriptions of the cross-sectional view of the line A-A', the cross-sectional view of the line B-B', and the cross-sectional view of the line C-C' of the semiconductor device are described in greater detail below.

(22) Referring to the one or more examples illustrated in FIG. 1A, an active region **200** including a drain region **210**, a source region **220**, a body pickup region **230**, and a deep well pickup region **240** may be formed on a substrate. Each of the regions **210**, **220**, **230**, and **240** of the active region **200** may be formed by using an active mask pattern, as a non-limiting example. The body contact region **230** and the deep well pickup region **240** may be spaced apart at a predetermined distance. A drain contact plug **211**, a source contact plug **221**, and a body contact plug **231** and a DNW contact plug **241** may be formed in the drain region **210**, the source region **220**, the body pickup region **230** and the deep well pickup region **240** of the active region **200**, respectively. The above-described contact plugs **211**, **221**, **231**, and **241** may be formed by including one or more of the contact plugs **211**, **221**, **231**, and **241** in a corresponding region. Although described in greater detail below, contact plugs, shown in FIG. 2A as **212**, **222**, **232**, **242** that are connected to metal wires may be formed on the contact plugs **211**, **221**, **231**, and **241**, respectively.

(23) Also, the gate region **110**, also referred to as a gate electrode **110**, may be formed between the source region **220** and the drain region **210**. That is, the source region **220** and the drain region **210** may be present on both sides of the gate electrode **110**, and the gate contact plug **111** may be formed on the gate electrode **110**.

(24) As illustrated in FIG. 1A the semiconductor device may include a first insulating film pattern **300** and a second insulating film pattern **400**. Because the first insulating film pattern **300** may be formed by etching an LDD insulating film, it may also be referred to as an LDD insulating film pattern. In addition, the second insulating film pattern **400** may be formed by using a silicon oxide

film or a silicon nitride film material so that a silicide or a silicide is not formed. Because the second insulating film pattern **400** is formed using such a non-sal process, it may be referred to as a non-sal dielectric pattern. The first insulating film pattern **300** and the second insulating film pattern **400** may be formed by using respective mask patterns, for example, as shown in FIGS. **9D** and **9H**. Each mask pattern may be designed using different layouts corresponding to the shapes of the first insulating film pattern **300** and the second insulating film pattern **400**. The first insulating film pattern **300** and the second insulating film pattern **400** may also be formed in various forms, which is illustrated in greater detail in other examples, to be described further later.

(25) In the present one or more examples, the shape, size, and area of the first insulating film pattern **300** may be determined by using a lightly doped region or lightly doped drain (LDD) forming process.

(26) Referring to FIG. **1A**, the first insulating film pattern **300** may be formed over a part of the source region **220** and the gate electrode **110**. That is, the first insulating film pattern **300** may be formed to extend to a top surface of the gate electrode **110**. Also, a part of the first insulating film pattern **300** may overlap the second insulating film pattern **400**. The first insulating film pattern **300** may extend to the top surface of the gate electrode, so as to have lengths **E1** and **E2**. The gate silicide layer **120** may be formed on the gate electrode **110**, where no first and second insulating film pattern **300** and **400** are formed. In such an example, the first insulating film pattern **300** may be divided into a first region having a length **E1**, and a second region having a length **E2**. The length of **E1** may be formed longer than **E2**. The longer the length of **E1**, the less the leakage current between the gate electrode **110** and the source region **220**. This result may occur because a resistance is increased between the gate electrode and the source region by the presence of the first insulating film pattern **300**.

(27) Referring to FIG. **1A**, the second insulating film pattern **400** may be a region in which the silicide layer **120** is not formed by the second mask pattern, for example, see FIG. **9H**. The second insulating film pattern **400** may be disposed entirely or partially on the top surfaces of the gate electrode **110** and the drain region **210**. Also, the second insulating film pattern **400** may overlap a part of the edge of the first insulating film pattern **300**. The second insulating film pattern **400** may be formed to extend onto a part of the gate electrode **110** and the drain region **210**. As such, the region **400** in which the silicide layer is not formed on the gate electrode **110** may be larger than the region **120** in which the silicide layer is formed. The resistance of the gate electrode **110** may be increased by the presence of the first insulating film pattern **300** and the second insulating film pattern **400**. Accordingly, it may be possible to prevent failure of a semiconductor device caused by an ESD or an EOS, due to such greater resistance.

(28) The second insulating film pattern **400** may include a main region **400a** and an extended region **400b**. The main region **400a** may be disposed to include a part of the top surface of the gate electrode **110** and to include a part of the drain region **210** where the first insulating film pattern **300** may partially overlap. The extension region **400b** may be formed to extend in the Y-axis direction so that the gate silicide layer **120** may remain at one end of the main region **400a**. As illustrated in FIG. **1A**, the main region **400a** may be larger in size than the extended region **400b**.

(29) In general, in order to form an Ohmic contact on the surface of the gate region, a silicide such as a cobalt silicide such as $\text{CoSi}_{2.2}$, or a nickel silicide such as NiSi , or a titanium silicide such as $\text{TiSi}_{2.2}$, may be formed. However, when a second insulating film pattern, such as a non-silicide region, is formed between the gate electrode **110** and the drain region **200** as illustrated in FIG. **1A**, resistance may increase between the gate electrode and the drain region, which may thereby reduce leakage current.

(30) FIG. **1B** illustrates a cross-section of a semiconductor device that is described in greater detail below. Each of the cross-sectional views, A-A', B-B', and C-C', is described in greater detail with reference to examples below. Referring to FIG. **1B**, a device isolation region, for example, a shallow trench isolation (STI) region, may be formed around the active region **200**.

(31) FIG. 2A is a cross-sectional view of a semiconductor device with respect to the line A-A' of FIG. 1B, according to one or more examples. Referring to the drawings, the semiconductor device may include a well region **20** of a first conductivity type, that is, as a non-limiting example, a P type, formed at a predetermined depth on the top surface of the substrate **10**. The well region **20** may be disposed between the device isolation regions **40** and **41** and may be formed to be deeper than the device isolation regions **40** and **41**.

(32) The gate insulating film **50** including the first gate insulating film **51** and the second gate insulating film **52**, which may have different thicknesses, are formed on the well region **20**. The gate electrode **110** may be disposed on the gate insulating film **50**. The drain region **210** and the source region **220** may be formed in the well region **20** and may be disposed on both sides, underneath the gate insulating film **50**.

(33) The gate insulating film **50** may include a first gate insulating film **51** and a second gate insulating film **52**, each having different thicknesses. For example, the first gate insulating film **51** may be thinner than the second gate insulating film **52**, and the second gate insulating film **52** may be formed to be thicker than the first gate insulating film **51**. The second gate insulating film **52** may be further divided into two parts. That is, the second gate insulating film **52** may have a part that becomes smaller in thickness as it approaches the first gate insulating film **51**, and may have a part that has a constant thickness in a direction of the spacer **60**. Such a part where the thickness becomes smaller as it approaches the first gate insulating film **51** may occur during the process of manufacturing the gate insulating film **50**. By using the gate insulating films **51** and **52** to have different thicknesses, it may be possible to implement a level shift semiconductor device in which a voltage used in a medium voltage or high voltage device may be allowed.

(34) The thinner first gate insulating film **51** may be disposed near the source region **220**, and the thick second gate insulating film **52** may be disposed near the drain region **210**. Such an approach may be used to prevent the gate insulating film **50** from being destroyed, because the drain voltage may be higher than the source voltage. For example, if the drain voltage is over 3.3V, which is a medium voltage, and the gate voltage is about 0.5V to 2V, which is a low voltage, there may be a problem that the drain current may become too low, and for this reason, the width of the channel region is to be widened, so that the region of the semiconductor device may be increased, if only a thick gate insulating film is used. Conversely, if only a thin gate insulating film is used, there may be an issue that the gate insulating film may be destroyed due to using a drain voltage higher than a medium voltage. Therefore, the above-described issue may be solved by using the gate insulating film **50** to have a structure that includes the thin gate insulating film **51** and the thick gate insulating film **52**.

(35) Because the drain voltage may be higher than the source voltage, the gate insulating film **50** may be formed to have an incline so that the thickness of the insulating film becomes thinner as it extends from the drain region to the source region. The drain region may be formed to be spaced apart by a predetermined distance from the gate electrode **110**, which may increase the breakdown voltage.

(36) The first insulating film pattern **300** and the spacer **60** may be formed on both sides of the gate electrode **110** and the gate insulating film **50**, respectively. Typically, only spacers are formed on both sides of the gate electrode **110**. However, in the present one or more examples, the first insulating film pattern **300** formed by using the first mask during the LDD process may be disposed near the source region **220** side, such that the source region **220** may overlap a part of the first insulating film pattern **300**. In addition, a spacer **60** may be formed on the drain region **210** side. The spacer **60** may be formed in the region in which no first insulating film pattern **300** is formed. Such an approach is used because the first insulating film may be formed as a spacer-shaped insulating film on all sides of the gate electrode **110** if a blanket etch-back process is performed without the first mask pattern. Thus, the first insulating film pattern **300** and the spacer insulating film **60** may be formed of the same material.

(37) The second insulating film pattern **400** may overlap a part of the first insulating film pattern **300** and may extend to the drain region **210**, while covering the top surface of the gate electrode **110** and the spacer **60**. The thickness of the second insulating film pattern **400** may be formed to be thicker than the first insulating film pattern **300**. For example, the second insulating film pattern **400** may be designed to have a sufficient thickness for proper operation. Such a choice of thickness may be made because when the second insulating film pattern **400** is thin, the second insulating film pattern **400** may be removed when various etching processes are performed in a subsequent process. For example, in such a case, an unwanted silicide layer may be formed, and using approaches according to examples may avoid such an undesired result.

(38) The semiconductor device may further include an extended drain junction region **80**. The extended drain junction region **80** may extend from the drain region **210** to the second gate insulating film **52**, in order to provide low drain resistance. As illustrated in FIG. 2A, the extended drain junction region **80** may have an additional length L that extends to the first gate insulating film **51**, which may be a thin gate insulating film. That is, the additional length of the extended drain junction region **80** may be disposed by freely adjusting the length between the gate insulating films **51** and **52**. Also, the extended drain junction region **80** may be formed to surround the drain region **210**, because an ion implantation may be performed with higher energy than that used for the drain region **210**. The extended drain junction region **80** may be formed by using N-type impurities, such as phosphorus or arsenic, as non-limiting examples. The depth of the extended drain junction region **80** may be formed to be thinner than the device isolation region **40** disposed next to the extended drain junction region **80**.

(39) The semiconductor device may further include a P-body region **90** of the first conductivity type, which may be P-type. The body region **90** may be located under the first gate insulating film **51**, which may be a thin gate insulating film, and may serve as a channel region. The body region **90** may surround the source region **220** and the body contact region **230**. The depth of the body region **90** may be thinner than the device isolation region **41** disposed next to the body region **90** and deeper than the extended drain junction region **80**. The body region **90** may be disposed to be spaced apart from the extended drain junction region **80** by a predetermined distance. In the absence of the body region **90**, the well region **20** of the first conductivity type may perform the channel region instead. Therefore, the body region **90** may be considered as an optional region. This choice may be made possible because the conductivity types of the body region and the well region are the same, that is, for example, both P-type, as a non-limiting example. An example in which the body region **90** is not formed is illustrated in FIG. 2B, below.

(40) The semiconductor device may further include a deep well region (DNW) **30** of the second conductivity type, which may be N-type. The deep well region **30** of the second conductivity type may be required when a semiconductor device and other devices are to be isolated. The deep well region **30** may be disposed between the device isolation regions **40** and **42**, and may include a well region **20** of a first conductivity type. A second conductivity type deep well pickup region **240** used for applying a bias voltage to the second conductivity type deep well region **30** may be further formed, in a non-limiting example.

(41) The semiconductor device may include isolation regions **40** and **41** formed next to the drain region **210** and the body pickup region **230** to isolate the semiconductor device from adjacent devices. The device isolation regions **40** and **41** may be formed using one of Shallow trench isolation (STI), Medium Trench Isolation (MTI), and Deep Trench Isolation (DTI) approaches. The device isolation regions **40** and **41** may use a LOCOS oxide film instead of a trench. In addition, the trench region may be formed by filling with a silicon oxide film (SiO₂), a silicon nitride film (SiN), or a polysilicon material, or the trench region may be formed by combining any two or more of the above-mentioned materials.

(42) The semiconductor device may include a body pickup region or body contact region **230** of a first conductivity type, located between the device isolation region **41** and the source region **220**.

The body pickup region **230** of the first conductivity type may be used for applying a ground voltage to the well region **20** of the first conductivity type or the body region **90** of the first conductivity type.

(43) As illustrated in FIG. 2A, the silicide layers **243**, **233**, **223**, and **213** may be disposed on a second conductivity type deep well contact region **240**, a body pickup region **230**, a part of a source region **220**, and a part of top surface of drain region **210**, according to a non-limiting example. A source contact plug **222** and a drain contact plug **212** may be respectively formed on the source silicide layer **223** and the drain silicide layer **213**. In addition, a body contact plug **232** and a deep well contact plug **242** may be formed on the body contact silicide layer **233** and the deep well contact silicide layer **243**, respectively. In such an example, the silicide layers **243**, **233**, **223**, and **213** may refer to regions in which materials such as a cobalt silicide such as CoSi.sub.2, a nickel silicide such as NiSi, a titanium silicide such as TiSi.sub.2, and the like, are formed. Thus, the material of the silicide layers **243**, **233**, **223**, **213** is made of a metal-silicide material, non-limiting examples of which are enumerated, above.

(44) In addition, the first insulating film pattern **300** of the semiconductor device according to one or more examples may partially overlap with the source region **220** and may be in contact with the source silicide layer **223**, and may be disposed to be spaced apart from the source contact plug **222** by a predetermined distance. The first insulating film pattern **300** may have a first region E1 formed on the substrate and may have a second region E2 formed on the gate electrode. The length of the first region E1 may be formed to be longer than the length of the second region E2, as shown in FIG. 1A. The first insulating film pattern **300** may be formed to directly contact the first conductivity type body region **90**, the source region **220**, and the source silicide layer **223**.

(45) The second insulating film pattern **400** may be thicker than the first insulating film pattern **300**, may be formed to be in contact with the first insulating film pattern **300**, and may be formed to extend onto the gate electrode **110**, the spacer **60**, and the drain region **210**. Therefore, the second insulating film pattern **400** may partially overlap the drain region **210** and may be in contact with the drain silicide layer **213**. Also, the second insulating film pattern **400** may be disposed to be spaced apart by a predetermined distance from the drain contact plug **212**. The second insulating film pattern **400** may have a third region formed on the substrate and a fourth region formed on the gate electrode, and the length of the third region may be formed to be shorter than the length of the fourth region. In addition, the second insulating film pattern **400** may be formed to directly contact the second conductivity type extended drain junction region **80**, the drain region **210**, and the drain silicide layer **213**, in a non-limiting example.

(46) Additionally, the top surface of the gate electrode **110** may be formed to be in direct contact with the gate silicide layer **120**, as shown in FIG. 3B, as well as the first insulating film pattern **300** and the second insulating film pattern **400**. In addition, the first and second insulating film patterns may be formed to be spaced apart by a predetermined distance from the gate contact plug **112**, as shown in FIG. 1A.

(47) FIG. 2B illustrates a structure where no P-type body region **90** is formed, in the semiconductor device of FIG. 2A described in greater detail, above. The overall structure may be the same as that of the example of FIG. 2A, but the structure of FIG. 2B may be a structure omitting the P-type body region **90** that was present in FIG. 2A. As illustrated in FIG. 2B, even if the P-type body region **90** does not exist, a well region, such as a P-type well region, of the first conductivity type may perform the role of the channel region. Therefore, the P-type body region **90** may not be always be formed in the semiconductor device of this example, such as is shown in FIG. 2B.

(48) FIG. 2C illustrates a structure in which the first insulating film pattern **300** and the P-type body region **90** are extended to be longer than in the semiconductor device illustrated in FIG. 2A. When compared to FIG. 2A, the distance between the sidewall of the gate electrode **110** and the source region **220** may be formed to be longer, in the example of FIG. 2C.

(49) Therefore, the first insulating film pattern **300** and the P-type body region **90** may be extended

as much as L1 and L2, respectively, in the example of FIG. 2C.

(50) FIG. 3A is a cross-sectional view illustrating each of the widths W of the first insulating film pattern **300** and the second insulating film pattern **400** of the semiconductor device, with respect to the line A-A' of FIG. 1A. FIG. 3A has the same cross-sectional structure as that of FIG. 2A described above, and thus the description of such a structure is omitted for brevity.

(51) As illustrated in FIG. 3A, the first insulating film pattern **300** disposed between the gate electrode **110** and the source region **220** may be formed to have a step with a height equal to the height of the gate electrode **110** and to have widths E1 and E2, where the width E1 may be greater than the width E2. As illustrated in the drawing of FIG. 3A, E1 and E2 may be formed from the ends of the source silicide layer **223** to the top surface of the gate electrode **110**. A part of the first insulating film pattern located on the top surface of the gate electrode **110** may partially overlap the second insulating film pattern **400**.

(52) In the second insulating film pattern **400**, the width E4 may include from the sidewall of the gate electrode **110** where the spacer **60** is formed, to the boundary of the drain silicide layer **213**. In addition, the second insulating film pattern **400** and the drain contact plug **212** may be formed to be spaced apart by a distance "D". The second insulating film pattern **400** and the drain contact plug **212** may be in contact with each other. However, in such a case, the length of the drain silicide layer **213** may be shortened, thereby increasing the contact resistance. Thus, it may be preferable to secure a distance "D" between the second insulating film pattern **400** and the drain contact plug **212**, to better control the contact resistance.

(53) FIG. 3B is a cross-sectional view taken along line B-B' in FIG. 1B, and FIG. 3C is a cross-sectional view taken along line C-C' in FIG. 1B.

(54) Referring to FIG. 3B, a second conductivity type deep well region **30** may be formed on the first conductivity type substrate **10**. A well region **20** of the first conductivity type may be formed in the deep well region **30**, wherein the source region and the drain region may be formed in the well region **20**. A device isolation region **43** may be formed on the well region **20** of the first conductivity type. A gate electrode **110** may also be formed on the device isolation region **43**.

(55) A first insulating film pattern **300** and a spacer **60** may be formed on both sides of the gate electrode **110**, respectively. A gate silicide layer **120**, a first insulating film pattern **300**, and a second insulating film pattern **400** may be formed on the gate electrode **110**. A gate contact plug **112** may be disposed on the gate silicide layer **120**.

(56) As illustrated in FIG. 3B, first insulating film patterns E1 and E2 and second insulating film patterns E3 and E4 may be formed on both sides of the gate electrode **110**, respectively. A gate silicide layer **120** may be formed on the top surface of the gate electrode **110** between the first insulating film pattern **300** and the second insulating film pattern **400**. In addition, each end of the first insulating film pattern E1 and the second insulating film pattern E3 may be formed to be spaced apart from the gate contact plug **112** by a predetermined distance. The individual ends of the first insulating film pattern E1 and the second insulating film pattern E3 may both be formed to be in contact with the gate contact plug **112** along with each other, but in this example, the length of the gate silicide layer **120** may be shortened, such that there is a disadvantage that the gate contact resistance may be increased. Therefore, it may be preferable that individual ends of the first insulating film pattern E1 and the second insulating film pattern E3 may be formed to be spaced apart from the gate contact plug **112** by a predetermined distance.

(57) Referring to the C-C' cross-sectional view of FIG. 3C, a first conductivity type well region **20** may be disposed between the portions of device isolation region **43**, and a gate insulating film **50** may be formed on the well region **20**. The gate insulating film **50** may be a gate insulating film including a first insulating film, having a thinner thickness, and a second insulating film, having a thicker thickness. A gate electrode **110** may be formed on the gate insulating film **50**, and a spacer **60** may be formed on a side of the gate electrode **110**. The gate electrode **110** may be formed on the first conductivity type well region **20**, and may be disposed to overlap a part of the top surface of

the device isolation region **43**.

(58) The second insulating film pattern **400** may be used for preventing the formation of silicide. The second insulating film pattern **400** may be formed of a material such as a silicon oxide (such as SiO₂) film, a silicon nitride film (SiN), or a silicon oxide nitride film (SiON) to have a predetermined thickness. As illustrated in FIG. 3C, the second insulating film pattern **400** may be spaced apart from the gate contact plug **112** by a predetermined distance, and may be formed on the gate electrode **110**, the spacer **60**, and the device isolation region **43**, according to a non-limiting example. On one end of the gate electrode, the spacer **60** may be formed on all of the region where the first insulating film pattern **300** is not formed. Thus, the one end of the gate electrode may be isolated from the substrate **10** by the first insulating film pattern **300** and the spacer **60**.

(59) FIG. 4 is a plan view of a semiconductor device, according to one or more examples. FIG. 4 is mostly similar to the structure of FIG. 1A, and only different in the structure of the first insulating film pattern **300**. For convenience of description, the same configuration as in FIG. 1A is denoted by the same reference numerals and the description of FIG. 4 focuses mainly on differences.

(60) Referring to FIG. 4, the semiconductor device may further include an extension unit **310** formed on a part of the upper part of the first insulating film pattern **300**. The extension unit **310** may have a shape in which one end of the first insulating film pattern **300** is in contact with the second insulating film, by being extended onto the first insulating film pattern **300**. Therefore, the first insulating film pattern **300** and the second insulating film pattern **400** may completely surround the gate contact plug **111**. Compared to FIG. 2A, in FIG. 4, the gate silicide layer **120** may be smaller with respect to the size of the extension unit **310**. Therefore, the resistance of the gate electrode illustrated in FIG. 4 may have a greater resistance than that of the gate electrode of FIG. 2A. Therefore, it may be possible to further reduce the leakage current in such a manner.

(61) FIG. 5 is a plan view of a semiconductor device, according to one or more examples. In FIG. 5, the second insulating film pattern **400** illustrated in the above-described examples may be formed to be smaller in size, and conversely, the first insulating film pattern **300** may be formed to be larger in size. For convenience of description, the first insulating film pattern **300** and the second insulating film pattern **400** may be principally described.

(62) Referring to FIG. 5, the first insulating film pattern **300** may be formed through a part of the gate electrode **110** and a part of the source region **220**, and the first insulating film pattern **300** may further include a pair of vertically symmetrical extension units **500a** and **500b**. The first insulating film pattern **300** may surround the gate electrode **110** by the extension units **500a** and **500b**, except for the drain region **210**. That is, the first insulating film pattern **300** may be formed to be in contact with all four surfaces of the gate electrode **110**. In addition, the first insulating film pattern **300** may be disposed to be spaced apart by a predetermined distance from the gate contact plug **111**.

(63) The second insulating film pattern **400** may include a part of the gate electrode **110**, and may be designed to be extended onto the drain region **210**. As illustrated in FIG. 5, the second insulating film pattern **400** may be spaced apart from one end **110a** of the gate electrode **110** that is in contact with the source region **220** and may overlap the other end **110b** of the gate electrode **110**. In addition, the second insulating film pattern **400** may be disposed spaced apart by a predetermined distance from the drain contact plug **211** and the gate contact plug **111**. The second insulating film pattern **400** may be formed to have a substantially rectangular shape from a top view.

(64) FIG. 6 is a plan view of a semiconductor device, according to one or more examples. Referring to FIG. 6, the sizes may be significantly reduced, as compared to the first insulating film pattern and the second insulating film pattern in other examples previously described.

(65) In FIG. 6, the first insulating film pattern **510** may be formed over the source region **220** and the gate electrode **110**. For example, in FIG. 6, E1 may be longer than E2. The first insulating film pattern **510** may be formed to be spaced apart from the source contact plug **221** by a predetermined distance. The second insulating film pattern **610** may be formed over the drain region **210**, from the gate electrode **110**. One end of the second insulating film pattern **610** may be formed to be in

contact with the first insulating film pattern **510**, and the other end of the second insulating film pattern **610** may be spaced apart from the drain contact plug **211** by a predetermined distance. (66) The size of the first insulating film pattern and the second insulating film pattern in FIG. **6** may shrink with respect to the other above-described examples, so that the gate silicide layer **120** may have a relatively larger area. In addition, at least three sides **110a**, **110b**, **110c** of the gate electrode **110** may be free from the first insulating film pattern **300** and the second insulating pattern **400**, according to such a non-limiting example.

(67) As illustrated in FIG. **6**, the first insulating film pattern **510** may extend toward the source region **220**. Likewise, the second insulating film pattern **610** may extend toward the drain region **210**. Thus, the first insulating film pattern **510** and the second insulating film pattern **610** may be partially enclosed by the gate contact plug **111**, the drain contact plug **211**, and the source contact plug **221**, as shown in the example of FIG. **6**.

(68) FIG. **7** is a plan view of a semiconductor device, according to one or more examples. FIG. **7** is a structure in which the first insulating film pattern **520** and the second insulating film pattern **620** may be spaced apart from each other. The first insulating film pattern **520** may be formed near the source region, and the second insulating film pattern **620** may be formed near the drain region. Referring to the drawing of FIG. **7**, the first insulating film pattern **520** may be formed to have a long bar shape that is parallel to the interface between the source region **220** and the gate electrode **110**. Also, the first insulating film pattern **520** may be disposed between the source contact plug **221** and the gate contact plug **111**.

(69) Because the first insulating film pattern **520** may be formed on a portion of the source region **220**, the resistance between the gate contact plug **111** and the source contact plug **221** may be increased. Therefore, the leakage current generated between the gate electrode **110** and the source region **220** of the semiconductor device may be reduced, as a result.

(70) In addition, a second insulating film pattern **620** may be formed between the gate electrode **110** and the drain region **210**. Therefore, a sufficient resistance may be secured between the gate electrode **110** and the drain region **210**, in order to reduce a leakage current.

(71) In addition, a spacer may be formed on the other end **110b**, **110c** of the gate electrode. A spacer may always be formed in a region where no first insulating film pattern **520** is formed. The spacer may even be formed under the second insulating film pattern **620**, because the first insulating film pattern **520** may not be formed under the second insulating film pattern **620**.

(72) FIG. **8** is a structure in which the second insulating film pattern further extends in the direction of the first insulating film pattern, when compared to FIG. **7** illustrated above. FIG. **8** otherwise has a structure generally similar to that of FIG. **1A**.

(73) Referring to FIG. **8**, the first insulating film pattern **530** may be a long bar shape disposed along the boundary surface between the source region **220** and the gate electrode **110**. The second insulating film pattern **630** may partially overlap the first insulating film pattern **530**, the gate electrode **110** and the drain region **210**, according to a non-limiting example. In addition, the second insulating film pattern **630** may extend in the Y-axis direction so as to surround the gate contact plug **111**.

(74) As illustrated in FIG. **8**, the gate contact plug **111** may be surrounded by the first insulating film pattern **530** and second insulating film pattern **630**, according to a non-limiting example. Therefore, ESD or EOS immunity in the device may increase, accordingly.

(75) Compared to FIG. **1A**, only the size of the first insulating film pattern **530** may be small in FIG. **8**. In addition, one end of the second insulating film pattern may be aligned with one end **110a** of the gate electrode **110**.

(76) A semiconductor device according to one or more examples, described above, may be manufactured by using the following method, illustrated in FIGS. **9A** to **9K**. FIGS. **9A** to **9K** show a process flow chart illustrating a method of manufacturing a semiconductor device step by step, and are described in greater detail with reference to the individual drawings, presented below.

(77) Referring to FIG. 9A, a second conductivity type deep well region **30** may be formed on a first conductivity type substrate **10**, and device isolation regions **40**, **41**, and **42** may be used to isolate from other devices by forming device isolation regions **40**, **41**, and **42** to a predetermined depth on the substrate **10**. Next, the well region **20** of the first conductivity type may be formed in the second conductivity type deep well region **30**. Alternatively, the device isolation regions **40**, **41**, and **42** may be formed first in the first conductivity type substrate **10**, and then the second conductivity type deep well region **30** and the first conductivity type well region **20** may be formed subsequently, in order.

(78) Referring to FIG. 9B, after forming a photoresist (PR) mask pattern **1** for forming an extended drain region **80**, ion implantation may be performed to form the second conductivity type, such as N type, extended drain region **80**, in the well region **20** of the first conductivity type, such as P type. The extended drain region **80** of the second conductivity type, such as N type, may be formed thinner than the device isolation region **40**. This extended drain region **80** may be formed to be thinner than the depth of the device isolation region **40** in order to electrically isolate from the adjacent extended drain region of other device regions. The PR mask pattern **1** may be removed, in such a non-limiting example.

(79) FIG. 9C illustrates a process of forming a P-type body region. The second PR mask pattern **2** for forming the P-type body region **90** may be formed, in a non-limiting example. Then, as illustrated in FIG. 9C, ion implantation may be performed to form the P-type body region **90**. A depth of the P-type body region **90** may be thinner than a depth of the device isolation region **41**, and the P-type body region **90** may be formed to be deeper than the extended drain region **80**. The P-type body region **90** may be spaced apart from the extended drain region **80**, or the P-type body region **90** and the extended drain region **80** may be in contact with each other.

(80) According to the present one or more examples, the process of forming the P-type body region **90** of FIG. 9C may occur before the formation of the extended drain region **80**. Also, the process of forming the P-type body region **90** may be omitted, in other examples. This approach may be possible because the well region **20** of the first conductivity type may perform the channel region instead, even though the P-type body region **90** may not be formed, as described above, according to other examples.

(81) Referring to FIG. 9D, after removing the PR mask pattern **2** for forming the P-type body region, gate insulating films **51** and **52** having different thicknesses may be formed. The thickness between the gate insulating films **51** and **52** may become thicker gradually as the gate insulating films **51** and **52** extend toward the drain region (X-axis).

(82) A gate electrode **110** may be formed on the gate insulating films **51** and **52**. The gate electrode **110** may be formed by depositing a conductive material for a gate electrode on the gate insulating films **51** and **52**, which may be formed by etching the conductive material after forming a mask pattern for the gate electrode on the conductive material.

(83) After forming the gate electrode **110**, lightly-doped-drain (LDD) ion implantation may be performed to form the LDD region **95** in the source region. LDD ion implantation may not be performed in the drain region because the extended drain region, such as a drift region, **80** may already be formed. The LDD region **95** may be formed to extend under the gate electrode, and the source region **220** may later be formed to overlap the LDD region. A channel region in the well region **20** may thus be formed between the N-type LDD region **95** and the N-type extended drain region.

(84) After forming the LDD region **95**, a first insulating film **310** of a predetermined thickness may be formed on the entire surface of the substrate **10**. As illustrated in the drawing of FIG. 9D, the first insulating film **310** may cover the entire surface of the substrate **10**, including the top and side surfaces of the gate electrode **110**. The first insulating film **310** may be etched to form the first insulating film pattern **300** later. As for the material of the first insulating film **310**, a material such as a silicon oxide film, a silicon nitride film, or a film combining two such films may be used, and

deposited by Low Pressure Chemical Vapor Deposition (LPCVD) or Plasma-Enhanced Chemical Vapor Deposition (PECVD) method, as non-limiting examples, in that the materials and the deposition techniques are not limited to these particular enumerated examples.

(85) The third mask pattern **3** may be formed on the first insulating film **310**. The third mask pattern **3** may be used for forming the first insulating film pattern **300** in the semiconductor device. The third mask pattern **3** may be designed in consideration of the structure of the first insulating film pattern **300** as well as the structure of the second insulating film pattern that is to be formed later.

(86) Referring to FIG. **9E**, the first insulating film **310** may be etched using the third mask pattern **3** as a mask. The gate electrode **110**, a part of the source region **90**, and a part of the drain region **80** may be exposed by such etching. The first insulating film pattern **300** may remain in the region that is covered by the third mask pattern **3**. The remaining region **300** may become such a first insulating film pattern **300**. In addition, a spacer may be formed on the other end of the gate electrode **110** during the etching process. Thus, a first insulating film pattern **300** on one end of the gate electrode **110** and a spacer **60** may be formed on the other end of the gate electrode **110**. A spacer insulating film **60** having a round shape may be formed by performing the etch-back process on the first insulating film **310**. Thereafter, the third mask pattern **3** may be removed.

(87) Referring to FIG. **9F**, a first ion-implantation having first conductivity type dopants may be performed in order to form a body pickup region **230**. A second ion-implantation having second conductivity type dopants may be performed to form a drain region **210**, a source region **220** and a deep well pickup region **240** of the second conductivity type. For example, the drain region **210** may be formed in the extended drain region **80**. On the other hand, the source region **220** and the body pickup region **230** may be formed in the P-type body region **90**. The drain region **210** may be in contact with the device isolation region **40**. The source region **220** may be formed to overlap a part of the first insulating film pattern **300**. The deep well pickup region **240** may be spaced apart by a predetermined distance from the body pickup region **230**, and may be disposed between the device isolation regions **41** and **42**.

(88) Next, the method may include a process of forming a second insulating film pattern. Referring to FIG. **9G**, a second insulating film **410** may be deposited at a predetermined thickness on top of the entire surface of the substrate **10** for the forming of a second insulating film pattern. Reference numeral **410** may be the second insulating film before etching. Later, when a part is etched according to the etching process, the second insulating film pattern **400** according to the present one or more examples may be formed.

(89) As illustrated in FIG. **9G**, the second insulating film **410** may be deposited to entirely cover the gate electrode **110**, the first insulating film pattern **300**, the spacer **60**, the extended drain region **980**, the drain region **210**, the source region **220**, the body pickup region **230**, the deep well pickup region **240** and the device isolation regions **40**, **41** and **42**, as a non-limiting example. The second insulating film **410** may be a material having the same constituent component materials as the first insulating film **310**. Alternatively, the second insulating film **410** may be formed of different materials from those of the first insulating film **310**, in order to have different etch selectivity with respect to the first insulating film pattern **300**. The thickness of the second insulating film **410** may be formed to be thicker than a thickness of the first insulating film **310**. In addition, the second insulating film **410** may be formed of a material such as a silicon oxide film (SiO or SiO.sub.2), a silicon nitride film (SiN), or a silicon oxide nitride film (SiON) at a predetermined thickness, as non-limiting examples of materials.

(90) As illustrated in FIG. **9H**, a fourth mask pattern **4** may be formed on a part of the top surface of the second insulating film **410**. The fourth mask pattern **4** may be formed only in a region where the second insulating film pattern **400** is to be formed. In the drawing, the fourth mask pattern **4** may be formed from the first insulating film pattern **300** to extend to a part of the drain region **210**.

(91) FIG. **9I** illustrates an etching process is performed on the second insulating film **410** by using

the fourth mask pattern **4** as a mask. Then, the second insulating film **410** may be selectively removed by the etching process, resulting in formation of the second insulating film pattern **400**, as illustrated in FIG. **9I**.

(92) FIG. **9J** illustrates a state in which the fourth mask pattern **4** is removed. As illustrated in FIG. **9J**, the second insulating film pattern **400** may be formed from the top surface of the first insulating film pattern **300** to extend to a part of the drain region **210**.

(93) Then, the silicide layers **213**, **223**, **233**, **243** may be respectively formed on the gate electrode **110**, the drain region **210**, the source region **220**, the body pickup region **230**, and the deep well pickup region **240**. Silicide layers **213**, **223**, **233**, **243** may be formed of silicides, such as cobalt silicide (CoSi.sub.2), nickel silicide (NiSi), and titanium silicide (TiSi.sub.2) materials, as non-limiting examples. The silicide layers may not be formed on the second insulating film pattern **400**, the first insulating film pattern **300**, and the spacer **60**, because those insulating films **60**, **300** and **400** may be used for blocking the formation of the silicide layers.

(94) After forming the silicide layers **213**, **223**, **233**, **243**, a borderless contact insulating film and an interlayer insulating film may be formed on the second insulating film pattern **400**, the first insulating film pattern **300** and the spacer **60**. The borderless contact insulating film and the interlayer insulating film may be each be regarded as a separate film that is different from the second insulating film pattern **400** and the first insulating film pattern **300**.

(95) As illustrated in FIG. **9K**, contact plugs **212**, **222**, **232**, **242** may be formed to respectively connect the drain region **210**, the source region **220**, the body pickup region **230**, and the deep well pickup region **240**. In order to form the contact plugs **212**, **222**, **232**, and **242**, a borderless contact insulating film and an interlayer insulating film may be partially etched to form a hole, and a metallic material such as tungsten (W) is used to fill the hole, as a non-limiting example, and Chemical Mechanical Planarization (CMP) may be performed.

(96) In summary, a manufacturing method of a semiconductor device, according to one or more examples may include, first, forming a deep well region and a device isolation region on a substrate, forming a well region of a first conductivity type in the deep well region, and forming a body region of a first conductivity type and an extended drain region of a second conductivity type on the well region of the first conductivity type.

(97) Also, a manufacturing method may include forming again a gate insulating film and a gate electrode on the substrate, forming a first insulating film on the entire region of the substrate, forming a first mask pattern on the first insulating film, forming a first insulating film pattern on one end of the gate electrode using the first mask pattern, and forming a spacer on the other end of the gate electrode, removing the first mask pattern, forming a source region on one end of the gate electrode, forming a drain region on the other end of the gate electrode, and forming a deep well pickup region and a body pickup region in the deep well region and the body region, respectively.

(98) Also, the manufacturing method may include depositing a second insulating film on the entire surface of the substrate, forming a second mask pattern on the second insulating film, removing the second insulating film formed on one end of the gate electrode using the second mask pattern, and forming a second insulating film pattern on the other end of the gate electrode and the spacer, removing the second mask pattern, forming a drain silicide layer on the drain region, forming a source silicide layer on the source region, and forming a drain contact plug and a source contact plug on the drain silicide layer and the source silicide layer, respectively. In addition, the first insulating film pattern and the second insulating film pattern may be in contact with each other.

(99) In the manufacturing process of FIGS. **9A-9K**, the structures of the first insulating film pattern **300** and the second insulating film pattern **400** may represent manufacturing processes based on the structure illustrated in FIG. **1A**. The first insulating film pattern **300** and the second insulating film pattern **400** may be formed by using respective mask patterns. Therefore, in case of forming the first insulating film pattern and the second insulating film pattern illustrated in FIGS. **4 to 8**, as described previously, the layout of the mask pattern may be changed. The first insulating film

pattern and the second insulating film pattern, having various shapes, may be formed only by changing the layout of the mask pattern.

(100) According to the semiconductor device and the method of manufacturing the semiconductor device of the one or more examples, as described above, it may be possible to prevent a leakage current between the gate electrode and the source region, by forming a first insulating film pattern on one end of the gate electrode in the direction of the source region, instead of forming a spacer.

(101) According to the semiconductor device and the method of manufacturing the semiconductor device of the one or more examples, a spacer and a second insulating film pattern may be formed on the other end of the gate electrode, toward the drain region, to prevent leakage current from occurring between the gate electrode and drain region.

(102) According to the semiconductor device and the method of manufacturing the semiconductor device of the one or more examples, there may be an effect of reducing the leakage current between the gate electrode-source region or the gate electrode-drain region by forming the first and second insulating film patterns to extend to the top surface of the gate electrode. Therefore, more stable semiconductor device function may be provided.

(103) While this disclosure includes specific examples, it will be apparent after an understanding of the disclosure of this application that various changes in form and details may be made in these examples without departing from the spirit and scope of the claims and their equivalents. The examples described herein are to be considered in a descriptive sense only, and not for purposes of limitation. Descriptions of features or aspects in each example are to be considered as being applicable to similar features or aspects in other examples. Suitable results may be achieved if the described techniques are performed in a different order, and/or if components in a described system, architecture, device, or circuit are combined in a different manner, and/or replaced or supplemented by other components or their equivalents. Therefore, the scope of the disclosure is defined not by the detailed description, but by the claims and their equivalents, and all variations within the scope of the claims and their equivalents are to be construed as being included in the disclosure.

Claims

1. A semiconductor device, comprising: an active region formed on a substrate of a first conductivity type; a source region, a drain region, and a gate insulating film respectively formed on the active region; a gate electrode formed on the gate insulating film; a first insulating film pattern extending from the source region to the gate electrode, contacting an upper surface of the source region and a side and upper surface of the gate electrode, and configured to prevent a silicide layer from forming on both the source region and the gate electrode where the first insulating film pattern is formed; an extended drain junction region of a second conductivity type under the gate electrode; and a second insulating film pattern contacting an upper surface of the extended drain junction region and the upper surface of the gate electrode, wherein each end of the first and second insulating film patterns overlap each other on the upper surface of the gate electrode.
2. The semiconductor device of claim 1, wherein the gate insulating film comprises a first gate insulating film having a first thickness and a second gate insulating film having a second thickness greater than the first thickness.
3. The semiconductor device of claim 2, wherein the extended drain junction region extends from the drain region to a region overlapping the first gate insulating film.
4. The semiconductor device of claim 1, further comprising: a well region of the first conductivity type formed on the substrate; a body region of the first conductivity type surrounding the source region; a lightly-doped-drain (LDD) region formed on a side surface of the source region; a body pickup region of the first conductivity type formed in the body region of the first conductivity type; a deep well region of the second conductivity type comprising the well region of the first

conductivity type; and a deep well pickup region of the second conductivity type formed in the deep well region of the second conductivity type.

5. The semiconductor device of claim 4, wherein the first insulating film pattern is in contact with the source region, the LDD region, and the upper surface of the gate electrode.
 6. The semiconductor device of claim 1, wherein the first insulating film pattern is thinner than the second insulating film pattern.
 7. A semiconductor device, comprising: an active region formed on a substrate of a first conductivity type; a source region, a drain region, and a gate insulating film respectively formed on the active region; a gate electrode formed on the gate insulating film; a first insulating film pattern extending from the source region to the gate electrode, in direct contact with a top surface of the source region and a side and top surface of the gate electrode, and configured to prevent a silicide layer from forming on both the source region and the gate electrode where the first insulating film pattern is formed; an extended drain junction region of a second conductivity type under the gate electrode; and a second insulating film pattern formed to contact the upper surface of the gate electrode and an upper surface of the extended drain junction region of the second conductivity type, wherein the second insulating film pattern is thicker than the first insulating film pattern.
 8. The semiconductor device of claim 7, wherein each one end of each of the first and second insulating film patterns overlaps each other on the upper surface of the gate electrode.
 9. The semiconductor device of claim 7, wherein the gate insulating film comprises a first gate insulating film having a first thickness and a second gate insulating film having a second thickness greater than the first thickness.
 10. The semiconductor device of claim 7, wherein the extended drain junction region extends from the drain region to a region overlapping the first gate insulating film.
 11. The semiconductor device of claim 7, further comprising: a well region of the first conductivity type formed on the substrate; a body region of the first conductivity type surrounding the source region; a lightly-doped-drain (LDD) region formed on a side surface of the source region; a body pickup region of the first conductivity type formed in the body region of the first conductivity type; a deep well region of the second conductivity type comprising the well region of the first conductivity type; and a deep well pickup region of the second conductivity type formed in the deep well region of the second conductivity type.
 12. The semiconductor device of claim 11, wherein the first insulating film pattern is in contact with the source region, the LDD region, and the upper surface of the gate electrode.
-