

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12410370
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Gold; Jeffrey W. et al.

Systems and methods for making hydrocarbon compositions derived from pyrolysis of post-consumer and/or post-industrial plastics

Abstract

Disclosed herein are methods for pyrolysis of plastic feedstock comprising post-consumer and/or post-industrial plastics. In various implementations, the methods include directing the plastic feedstock into an internal volume of a reactor vessel, and pyrolyzing the plastic feedstock in the internal volume of the reactor vessel.

Inventors:	Gold; Jeffrey W. (Atlanta, GA), Cudney; Connor (Atlanta, GA)
Applicant:	Nexus Circular LLC (Atlanta, GA)
Family ID:	96501676
Assignee:	Nexus Circular LLC (Atlanta, GA)
Appl. No.:	19/006100
Filed:	December 30, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20250243411 A1	Jul. 31, 2025

Related U.S. Application Data

us-provisional-application US 63626488 20240129

Publication Classification

Int. Cl.: C10B53/07 (20060101); C10B47/18 (20060101); C10G1/02 (20060101); C10B19/00 (20060101)

U.S. Cl.:

CPC **C10B53/07** (20130101); **C10B47/18** (20130101); **C10G1/02** (20130101); C10B19/00 (20130101); C10G2300/1003 (20130101)

Field of Classification Search

CPC: C10B (19/00); C10B (47/18); C10B (53/07); C10G (1/02); C10G (2300/1003)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3901961	12/1974	Goerter et al.	N/A	N/A
3940233	12/1975	Fox et al.	N/A	N/A
3947256	12/1975	Tsukagoshi	N/A	N/A
3952053	12/1975	Brown, Jr. et al.	N/A	N/A
3984288	12/1975	Yoshida	N/A	N/A
4208252	12/1979	Yoshida	N/A	N/A
4851601	12/1988	Fukuda et al.	N/A	N/A
5135638	12/1991	Miller	N/A	N/A
5208005	12/1992	Miller	N/A	N/A
5216149	12/1992	Evans et al.	N/A	N/A
5253479	12/1992	Di Cintio et al.	N/A	N/A
5292862	12/1993	Miura et al.	N/A	N/A
5300704	12/1993	Evans et al.	N/A	N/A
5321174	12/1993	Evans et al.	N/A	N/A
5354930	12/1993	Atkins et al.	N/A	N/A
5359061	12/1993	Evans et al.	N/A	N/A
5359099	12/1993	Evans et al.	N/A	N/A
5364985	12/1993	Hermanson	N/A	N/A
5364995	12/1993	Kirkwood et al.	N/A	N/A
5481052	12/1995	Hardman et al.	N/A	N/A
5523502	12/1995	Rubin	N/A	N/A
5542372	12/1995	Sun et al.	N/A	N/A
5584969	12/1995	Nagai	N/A	N/A
5608136	12/1996	Maezawa et al.	N/A	N/A
5639937	12/1996	Hover et al.	N/A	N/A
5731483	12/1997	Stabel	N/A	N/A
5738025	12/1997	Tachibana	N/A	N/A
5744668	12/1997	Zhou et al.	N/A	N/A
5821553	12/1997	Evans et al.	N/A	N/A
5824193	12/1997	Edwards	N/A	N/A
5849964	12/1997	Holighaus et al.	N/A	N/A
5904838	12/1998	Kalnes et al.	N/A	N/A
6011187	12/1999	Horizoe	N/A	N/A
6048380	12/1999	Asanuma	N/A	N/A
6111156	12/1999	Oballa et al.	N/A	N/A
6143940	12/1999	Miller et al.	N/A	N/A

6150577	12/1999	Miller et al.	N/A	N/A
6288296	12/2000	Miller et al.	N/A	N/A
6346220	12/2001	Kosugi	N/A	N/A
6620895	12/2002	Cotts	264/564	B29C 67/24
6703535	12/2003	Johnson et al.	N/A	N/A
6774272	12/2003	Miller	N/A	N/A
6777581	12/2003	Zmuda	N/A	N/A
6808305	12/2003	Sharpe	366/168.1	B01D 37/03
6822126	12/2003	Miller	N/A	N/A
6881303	12/2004	Inoue	N/A	N/A
H2118	12/2004	Winter	N/A	N/A
RE40124	12/2007	Kaiser et al.	N/A	N/A
7452392	12/2007	Nick et al.	N/A	N/A
7604791	12/2008	Sato	N/A	N/A
7714178	12/2009	Bylicki et al.	N/A	N/A
7758729	12/2009	Dewhitt	N/A	N/A
7834226	12/2009	Miller	N/A	N/A
7862651	12/2010	Stein et al.	N/A	N/A
7867959	12/2010	Miller et al.	N/A	N/A
7968006	12/2010	Johnson et al.	N/A	N/A
7968022	12/2010	Brooks et al.	N/A	N/A
8017040	12/2010	Johnson et al.	N/A	N/A
8017041	12/2010	Johnson et al.	N/A	N/A
8021577	12/2010	Johnson et al.	N/A	N/A
8088961	12/2011	Miller	N/A	N/A
8137508	12/2011	Grispin	N/A	N/A
8187428	12/2011	Shimo	N/A	N/A
8192586	12/2011	Garrison et al.	N/A	N/A
8192587	12/2011	Garrison et al.	N/A	N/A
8222471	12/2011	Elomari et al.	N/A	N/A
8323589	12/2011	Hamby et al.	N/A	N/A
8404912	12/2012	Miller	N/A	N/A
8420875	12/2012	Mackay et al.	N/A	N/A
8460410	12/2012	Tsang et al.	N/A	N/A
8480880	12/2012	Miller	N/A	N/A
8500959	12/2012	Lehto	N/A	N/A
8524968	12/2012	Elomari et al.	N/A	N/A
8552245	12/2012	Simon et al.	N/A	N/A
8575081	12/2012	Miller et al.	N/A	N/A
8581015	12/2012	Jeon	N/A	N/A
8668810	12/2013	Vardanyan et al.	N/A	N/A
8674154	12/2013	Podeszfa	N/A	N/A
8680349	12/2013	Fraczak	N/A	N/A
8696994	12/2013	Miller	N/A	N/A
8864946	12/2013	Scheirs	N/A	N/A
8927797	12/2014	Sarker	N/A	N/A
8975459	12/2014	Vermeiren et al.	N/A	N/A
9017522	12/2014	Gildenhuys et al.	N/A	N/A

9074140	12/2014	Fraczak	N/A	N/A
9080107	12/2014	Fraczak et al.	N/A	N/A
9096801	12/2014	Baker	N/A	N/A
9109238	12/2014	Miller et al.	N/A	N/A
9309452	12/2015	Elomari et al.	N/A	N/A
9365775	12/2015	La Crosse et al.	N/A	N/A
9376632	12/2015	Fraczak	N/A	N/A
9399179	12/2015	Venter et al.	N/A	N/A
9404046	12/2015	Sarker	N/A	N/A
9428695	12/2015	Narayanaswamy et al.	N/A	N/A
9447332	12/2015	Narayanaswamy et al.	N/A	N/A
9714391	12/2016	Combs	N/A	N/A
10093860	12/2017	Griffiths	N/A	N/A
10106750	12/2017	Gutierrez et al.	N/A	N/A
10131847	12/2017	McNamara	N/A	N/A
10233393	12/2018	Oluwaseun et al.	N/A	N/A
10294433	12/2018	Grainger et al.	N/A	N/A
10301235	12/2018	Cavinaw et al.	N/A	N/A
10377951	12/2018	Vanttinen et al.	N/A	N/A
10421911	12/2018	Ullom	N/A	N/A
10442997	12/2018	Narayanaswamy et al.	N/A	N/A
10472487	12/2018	Gil et al.	N/A	N/A
10513661	12/2018	Narayanaswamy et al.	N/A	N/A
10518242	12/2018	Van Cauwenberge et al.	N/A	N/A
10519047	12/2018	Johnson et al.	N/A	N/A
10519077	12/2018	Kreischer	N/A	N/A
10551059	12/2019	Inskip	N/A	N/A
10598882	12/2019	Bohler et al.	N/A	N/A
10717934	12/2019	Griffiths	N/A	N/A
10731082	12/2019	Tenore et al.	N/A	N/A
10738244	12/2019	Ershag et al.	N/A	N/A
10814525	12/2019	Geronimi	N/A	N/A
10858593	12/2019	Ramamurthy et al.	N/A	N/A
10899991	12/2020	Atkins et al.	N/A	N/A
10968394	12/2020	Posmyk et al.	N/A	N/A
11015127	12/2020	Geronimi	N/A	N/A
11041123	12/2020	Cavinaw et al.	N/A	N/A
11072693	12/2020	Gil et al.	N/A	N/A
11091700	12/2020	Atkins et al.	N/A	N/A
11136507	12/2020	Niu et al.	N/A	N/A
11174436	12/2020	Timken	N/A	N/A
11174437	12/2020	Timken	N/A	N/A
11254877	12/2021	Rooney et al.	N/A	N/A
11306253	12/2021	Timken et al.	N/A	N/A
11339330	12/2021	Humphreys et al.	N/A	N/A

11359147	12/2021	Timken	N/A	N/A
11365357	12/2021	Bitting et al.	N/A	N/A
11447402	12/2021	Johnson et al.	N/A	N/A
11471817	12/2021	Kurkijärvi et al.	N/A	N/A
11473015	12/2021	Ershag et al.	N/A	N/A
11473016	12/2021	Timken	N/A	N/A
11473017	12/2021	Horlacher	N/A	N/A
11479726	12/2021	Abbott et al.	N/A	N/A
11518940	12/2021	Chia	N/A	N/A
11518942	12/2021	Abbott et al.	N/A	N/A
11518943	12/2021	Timken	N/A	N/A
11518944	12/2021	Timken	N/A	N/A
11518945	12/2021	Timken	N/A	N/A
11530358	12/2021	Bertrand et al.	N/A	N/A
11530359	12/2021	Sarker et al.	N/A	N/A
11530539	12/2021	Roh et al.	N/A	N/A
11566182	12/2022	Timken et al.	N/A	N/A
11584890	12/2022	Timken	N/A	N/A
11603338	12/2022	Yun et al.	N/A	N/A
11618855	12/2022	Abbott et al.	N/A	N/A
11639472	12/2022	Timken	N/A	N/A
11732197	12/2022	Timken	N/A	N/A
11739191	12/2022	Gil et al.	N/A	N/A
11739272	12/2022	Timken	N/A	N/A
11746297	12/2022	Abbott et al.	N/A	N/A
11746298	12/2022	Kapaun et al.	N/A	N/A
11773330	12/2022	Tenore et al.	N/A	N/A
11781073	12/2022	Abbott et al.	N/A	N/A
11795401	12/2022	Chakraborty et al.	N/A	N/A
11802250	12/2022	Murray et al.	N/A	N/A
11845900	12/2022	Atkins et al.	N/A	N/A
11884884	12/2023	Gold et al.	N/A	N/A
11884885	12/2023	Liu et al.	N/A	N/A
11891518	12/2023	Gold et al.	N/A	N/A
11905466	12/2023	Timken	N/A	N/A
11920089	12/2023	Dockter et al.	N/A	N/A
11920094	12/2023	Derks	N/A	N/A
11939527	12/2023	Timken et al.	N/A	N/A
11939530	12/2023	Löw	N/A	N/A
11939531	12/2023	Paasikallio et al.	N/A	N/A
11952545	12/2023	Gold	N/A	N/A
11959025	12/2023	Timken	N/A	N/A
11964315	12/2023	Gold et al.	N/A	N/A
11969689	12/2023	Kurkijärvi et al.	N/A	N/A
11981779	12/2023	Parrott et al.	N/A	N/A
12018213	12/2023	Besong	N/A	N/A
12031091	12/2023	Slivensky et al.	N/A	N/A
12077713	12/2023	Abbott et al.	N/A	N/A
2004/0235655	12/2003	Sato et al.	N/A	N/A
2009/0151233	12/2008	Miller	N/A	N/A

2009/0170739	12/2008	Miller	N/A	N/A
2011/0020190	12/2010	Miller	N/A	N/A
2011/0072967	12/2010	Wood et al.	N/A	N/A
2011/0230689	12/2010	Scheirs	N/A	N/A
2011/0289826	12/2010	Srinakruang	N/A	N/A
2012/0070347	12/2011	Bacon et al.	N/A	N/A
2012/0184787	12/2011	Miller	N/A	N/A
2013/0184505	12/2012	Maxwell	N/A	N/A
2014/0228204	12/2013	Narayanaswamy et al.	N/A	N/A
2014/0228205	12/2013	Narayanaswamy et al.	N/A	N/A
2014/0228605	12/2013	Narayanaswamy et al.	N/A	N/A
2014/0228606	12/2013	Narayanaswamy et al.	N/A	N/A
2015/0247096	12/2014	Barger et al.	N/A	N/A
2016/0090539	12/2015	Frey et al.	N/A	N/A
2016/0137932	12/2015	Kulprathipanja et al.	N/A	N/A
2016/0264874	12/2015	Narayanaswamy et al.	N/A	N/A
2016/0264883	12/2015	Narayanaswamy et al.	N/A	N/A
2016/0264885	12/2015	Narayanaswamy et al.	N/A	N/A
2016/0362609	12/2015	Ward et al.	N/A	N/A
2017/0044465	12/2016	Scheibel et al.	N/A	N/A
2017/0283706	12/2016	Schabel et al.	N/A	N/A
2017/0327663	12/2016	Gil et al.	N/A	N/A
2018/0002609	12/2017	Narayanaswamy et al.	N/A	N/A
2018/0187087	12/2017	Atkins et al.	N/A	N/A
2018/0273848	12/2017	Atkins et al.	N/A	N/A
2019/0016960	12/2018	Griffiths	N/A	N/A
2019/0144755	12/2018	Atkins et al.	N/A	N/A
2019/0161683	12/2018	Narayanaswamy et al.	N/A	N/A
2019/0177626	12/2018	Ramamurthy et al.	N/A	N/A
2019/0177652	12/2018	Atkins et al.	N/A	N/A
2019/0233744	12/2018	Narayanaswamy et al.	N/A	N/A
2019/0241838	12/2018	Scheibel et al.	N/A	N/A
2019/0284476	12/2018	Gaber et al.	N/A	N/A
2019/0299491	12/2018	Stanislaus et al.	N/A	N/A
2019/0367428	12/2018	Ramamurthy et al.	N/A	N/A
2019/0382672	12/2018	Sorensen	N/A	N/A
2020/0017772	12/2019	Ramamurthy et al.	N/A	N/A
2020/0017773	12/2019	Ramamurthy et al.	N/A	N/A
2020/0071619	12/2019	Humphreys et al.	N/A	N/A
2020/0080009	12/2019	Derks	N/A	N/A

2020/0181498	12/2019	Heeres et al.	N/A	N/A
2020/0308492	12/2019	Streiff et al.	N/A	N/A
2020/0362248	12/2019	Cartolano et al.	N/A	N/A
2020/0369965	12/2019	Bitting et al.	N/A	N/A
2020/0369966	12/2019	Bitting et al.	N/A	N/A
2021/0032545	12/2020	Harandi et al.	N/A	N/A
2021/0061972	12/2020	Nagy et al.	N/A	N/A
2021/0070958	12/2020	Brita et al.	N/A	N/A
2021/0070959	12/2020	Brita et al.	N/A	N/A
2021/0108154	12/2020	Schiebel et al.	N/A	N/A
2021/0122989	12/2020	White	N/A	N/A
2021/0130262	12/2020	Wu et al.	N/A	N/A
2021/0130698	12/2020	Sundaram	N/A	N/A
2021/0130699	12/2020	Bitting et al.	N/A	N/A
2021/0130700	12/2020	Wu et al.	N/A	N/A
2021/0139620	12/2020	Slivensky et al.	N/A	N/A
2021/0189248	12/2020	Timken	N/A	N/A
2021/0189249	12/2020	Timken	N/A	N/A
2021/0189250	12/2020	Timken	N/A	N/A
2021/0189251	12/2020	Timken	N/A	N/A
2021/0189252	12/2020	Timken	N/A	N/A
2021/0189253	12/2020	Timken	N/A	N/A
2021/0189254	12/2020	Timken	N/A	N/A
2021/0284818	12/2020	Doucet et al.	N/A	N/A
2021/0301209	12/2020	Timken et al.	N/A	N/A
2021/0301210	12/2020	Timken	N/A	N/A
2021/0332299	12/2020	Timken	N/A	N/A
2021/0332300	12/2020	Timken	N/A	N/A
2021/0363432	12/2020	Bitting et al.	N/A	N/A
2022/0010211	12/2021	Allegro, II et al.	N/A	N/A
2022/0010212	12/2021	Shi et al.	N/A	N/A
2022/0010213	12/2021	Sun et al.	N/A	N/A
2022/0010217	12/2021	Barger et al.	N/A	N/A
2022/0010218	12/2021	Davydov	N/A	N/A
2022/0041905	12/2021	Boaventura et al.	N/A	N/A
2022/0065535	12/2021	Schabel	N/A	F27D 13/00
2022/0073826	12/2021	Van Zijl et al.	N/A	N/A
2022/0081372	12/2021	Niessner et al.	N/A	N/A
2022/0081634	12/2021	Arnst et al.	N/A	N/A
2022/0098045	12/2021	Stapela	N/A	C01B 33/12
2022/0098490	12/2021	Abbott et al.	N/A	N/A
2022/0098491	12/2021	Abbott et al.	N/A	N/A
2022/0154077	12/2021	Bitting et al.	N/A	N/A
2022/0195311	12/2021	Low	N/A	N/A
2022/0204870	12/2021	Portela et al.	N/A	N/A
2022/0220391	12/2021	Slivensky et al.	N/A	N/A
2022/0228070	12/2021	Chakraborty et al.	N/A	N/A
2022/0289648	12/2021	Arnst et al.	N/A	N/A

2022/0363994	12/2021	Besong et al.	N/A	N/A
2022/0363996	12/2021	Wu et al.	N/A	N/A
2022/0389327	12/2021	Reimers	N/A	N/A
2022/0396735	12/2021	Wu et al.	N/A	N/A
2022/0396736	12/2021	Wu et al.	N/A	N/A
2023/0039224	12/2022	Bozzano et al.	N/A	N/A
2023/0067668	12/2022	Abbott et al.	N/A	N/A
2023/0117658	12/2022	Bitting et al.	N/A	N/A
2023/0272293	12/2022	Weiss et al.	N/A	N/A
2023/0312437	12/2022	Schmidt et al.	N/A	N/A
2023/0312438	12/2022	Timken	N/A	N/A
2023/0312439	12/2022	Timken	N/A	N/A
2023/0312862	12/2022	Liu et al.	N/A	N/A
2023/0313052	12/2022	Timken	N/A	N/A
2023/0348342	12/2022	Timken	N/A	N/A
2023/0407183	12/2022	Abbott et al.	N/A	N/A
2024/0010583	12/2023	Schmidt et al.	N/A	N/A
2024/0010927	12/2023	Liu et al.	N/A	N/A
2024/0010928	12/2023	Schmidt et al.	N/A	N/A
2024/0010940	12/2023	Liu et al.	N/A	N/A
2024/0182793	12/2023	Mathias Aloysius Becker Neto et al.	N/A	N/A
2024/0384173	12/2023	McNamara et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2287564	12/2000	CA	N/A
3226858	12/2020	CA	N/A
1025186	12/1999	EP	N/A
2406348	12/2011	EP	N/A
3784756	12/2020	EP	N/A
3950889	12/2021	EP	N/A
4108737	12/2021	EP	N/A
4141088	12/2022	EP	N/A
H0256769	12/1993	JP	N/A
H0841465	12/1995	JP	N/A
H11-302663	12/1998	JP	N/A
2009087080	12/2008	WO	N/A
2017167947	12/2016	WO	N/A
2018011642	12/2017	WO	N/A
2020152317	12/2019	WO	N/A
2020216893	12/2019	WO	N/A
2020242914	12/2019	WO	N/A
2020247192	12/2019	WO	N/A
2020252228	12/2019	WO	N/A
2021133881	12/2020	WO	N/A
2021201932	12/2020	WO	N/A
2020242912	12/2021	WO	N/A
2022093131	12/2021	WO	N/A

2022193015	12/2021	WO	N/A
2022213021	12/2021	WO	N/A
2023038855	12/2022	WO	N/A
2023187732	12/2022	WO	N/A

OTHER PUBLICATIONS

Plastic Additives by Grace (Year: 2024). cited by examiner

Enabling a circular economy for chemicals with the mass balance approach, A white paper from co.project mass balance, Ellen Macarthur Foundation, 2019, 35 pages. cited by applicant

Somoza-Tornos A et al. Realizing the Potential High Benefits of Circular Economy in the Chemical Industry: Ethylene Monomer Recovery via Polyethylene Pyrolysis, ACS Sustainable Chemistry & Engineering 2020, 8, 3561-3572. cited by applicant

Miandad R et al. Catalytic Pyrolysis of Plastic Waste: Moving Toward Pyrolysis Based Biorefineries. Fronteier in Energy Research, 2019, 7, 27 (17 pages). cited by applicant

Miller SJ et al. Conversion of Waste Plastic to Lubricating Base Oil, Energy & Fuels 2005, 19, 1580-1586. cited by applicant

Sarker M et al. Mixture of LDPE, PP and PS Waste Plastics into Fuel by Thermolysis Process, International Journal of Engineering and Technology Research, 2013, 1(1), 16 pages. cited by applicant

Garieb Alla MM et al. Simulation and Design for Process to Convert Plastic Waste to Liquid Fuel Using Aspen Hysys Program, Integer. J. Engg. Res. Tech. 2014, 1(6), 270-274. cited by applicant

Fivga A et al. Pyrolysis of plastic waste for production of heavy fuel substitute: A techno-economic assessment, Energy (2018), doi: 10.1016/j.energy.2018.02.094. cited by applicant

Adeniyi AG et al. Computer Aided Modelling of Low Density Polyethylene Pyrolysis to Produce Synthetic Fuels, Nigerian Journal of Technology, 2018, 37(4), 945-959. cited by applicant

Selvaganapathy T et al. Simulation of Waste Plastic Pyrolysis Process Using Aspen Hysys V9 Simulator under Steady State Operating Condition, Chapter 11, Emerging Trends in Engineering Research and Technology vol. 2, 2020, pp. 108-118. cited by applicant

Tollini F et al. Influence of the catalytic system on the methanolysis of polyethylene terephthalate at mild conditions: A systematic investigation, Chemical Engineering Science, 2022, 260, 117875. cited by applicant

Jeya G et al. A short review on latest developments in catalytic depolymerization of Poly(ethylene terephthalate) wastes, Journal of the Indian Chemical Society, 2022, 99, 100291. cited by applicant

Xin J et al. Progress in the catalytic glycolysis of polyethylene terephthalate, journal of Environmental Management, 2021, 296, 113267. cited by applicant

Liu Y et al. Catalytic depolymerization of polyethylene terephthalate in hot compressed water, The Journal of Supercritical Fluids, 2012, 62, 226-231. cited by applicant

Khan A et al. Efficient chemical recycling of waste polyethylene terephthalate, Resources, Conservation & Recycling, 2022, 187, 106639. cited by applicant

Pashan RK et al. Chemical Depolymerization of PET Bottles via Combined Chemolysis Methods. Chapter 7, Recycling of Polyethylene Terephthalae Bottles, 2019, pp. 135-147. cited by applicant

Langer E et al. Method of PET Recycling, Plasticizers derived from Post-Consumer PET, chapter 5, pp. 127-171. cited by applicant

Biermann L et al. Development of a continuous PET depolymerization process as a basis for a back-to-monomer recycling method, Green Processing and Synthesis 2021; 10: 361-373. cited by applicant

Tullo AH. Plastic has a problem, is chemistry the solution? Chemical and Engineering News, 2019, 97(39), 8 pages. cited by applicant

Tullo A. Chemical firms back depolymerization. Chemical and Engineering News, 2018, 96(39), 1

page. cited by applicant

Hofmann M et al. Zinc(II) acetate Catalyzed Depolymerization of Poly(ethylene terephthalate), *Chemistry Select*, 2020, 5, 10010-10014. cited by applicant

Tournier V et al. An engineered PET depolymerase to break down and recycle plastic bottles, *Nature*, 2020, 580, 216. cited by applicant

Garcia JM et al. The future of plastics recycling, *Science*, 2017, 358, 870. cited by applicant

Chen JY et al. Depolymerization of poly(ethylene terephthalate) resin under pressure, *Journal of Applied Polymer Science*, 1991, 42(6), 1501-1507. cited by applicant

Zope VS et al. Kinetics of Neutral Hydrolytic Depolymerization of PET (Polyethylene Terephthalate) Waste at Higher Temperature and Autogenous Pressures, *Journal of Applied Polymer Science*, 2008, 110, 2179-2183. cited by applicant

Kao et al. Kinetics of Hydrolytic Depolymerization of Melt Poly(ethylene terephthalate), *Ind. Eng. Chem. Res.* 1998, 37, 1228-1234. cited by applicant

Guo Z. et al. An efficient recycling process of glycolysis of PET in the presence of a sustainable nanocatalyst, *Journal of Applied Polymer Science*, 2018, 135(21), 46285. cited by applicant

Ma M et al. Insights into the depolymerization of polyethylene terephthalate in methanol, *Journal of Applied Polymer Science*, 2022, 139(35), e52814. cited by applicant

Zenda K et al. Depolymerization of poly(ethylene terephthalate) in dilute aqueous ammonia solution under hydrothermal , conditions. *J Chem Technol Biotechnol* 83:1381-1386 (2008). cited by applicant

Fukushima K et al. Organocatalytic Depolymerization of Poly(ethylene terephthalate), *Journal of Polymer Science Part A: Polymer Chemistry*, vol. 49, 1273-1281 (2011). cited by applicant

Goje AS et al. Chemical Kinetics, Simulation, and Thermodynamics of Glycolytic Depolymerization of Poly(ethylene terephthalate) Waste with Catalyst Optimization for Recycling of Value Added Monomeric Products, *Macromol. Mater. Eng.* 2003, 288, 326-336. cited by applicant

Makower J. Inside Eastman's moonshot goal for endlessly circular plastics, 2020, <https://trellis.net/article/inside-eastmans-moonshot-goal-endlessly-circular-plastics/>, Accessed Mar. 3, 2025. cited by applicant

Tricker AW et al. Stages and Kinetics of Mechanochemical Depolymerization of Poly(ethylene terephthalate) with Sodium Hydroxide, *ACS Sustainable Chem. Eng.* 2022, 10, 11338-11347. cited by applicant

Pudak C et al. PET Recycling—Contributions of Crystallization to Sustainability, *Chem. Ing. Tech.* 2020, 92, No. 4, 452-458. cited by applicant

Khoonkari M et al. Chemical Recycling of PET Wastes with Different Catalysts, *Hindawi Publishing Corporation International Journal of Polymer Science*, vol. 2015, Article ID 124524, 11 pages, <http://dx.doi.org/10.1155/2015/124524>. cited by applicant

Singh A et al. Techno-economic, life-cycle, and socioeconomic impact analysis of enzymatic recycling of poly(ethylene terephthalate), *Joule* 2021, 5, 2479-2503. cited by applicant

Dzhabarov, G.V., et al., A kinetic study on the depolymerization of polyethylene terephthalate waste with crude glycerol. *Chemical Papers*, 2021. 75(11): p. 6035-6046. cited by applicant

Zhao YB et al. Solvent-based separation and recycling of waste plastics: A review. *Chemosphere*, 2018. 209: p. 707-720. cited by applicant

Hajighasemi, M., et al., Biochemical and Structural Insights into Enzymatic Depolymerization of Polylactic Acid and Other Polyesters by Microbial Carboxylesterases. *Biomacromolecules*, 2016. 17(6), 2027. cited by applicant

Zhang, L.N., et al., From Aminolysis Product of PET Waste to Value-added Products of Polymer and Assistants. *Polymers & Polymer Composites*, 2014. 22(1): p. 13-16. cited by applicant

Goto, M., Chemical recycling of plastics using sub- and supercritical fluids. *The Journal of Supercritical Fluids*, 2009. 47(3): p. 500-507. cited by applicant

Krehula, L.K., et al., Study of PET depolymerization during recycling. *E-Polymers*, 2008: 089, 12 pages. cited by applicant

“Cracking the problem of waste plastic,” ISCC Press Release dated Apr. 15, 2019, <https://www.iscc-system.org/news/cracking-the-problem-of-waste-plastics/>, Accessed Mar. 3, 2025. cited by applicant

Al-Salem SM et al. A review on thermal and catalytic pyrolysis of plastic solid waste (PSW), *Journal of Environmental Management* 197 (2017) 177-198. cited by applicant

Kaminsky W et al. Recycling of polymers by pyrolysis. *Journal de Physique IV Proceedings*, 1993, 03 (C7), pp. C7-1543-C7-1552. cited by applicant

Kiran N et al. Recycling of plastic wastes via pyrolysis, *Resources, Conservation and Recycling* 29 (2000) 273-283. cited by applicant

Laermann M. Chemical Recycling of Plastic—Waste No More? Apr. 10, 2019. <https://global-recycling.info/archives/3236>, Accessed Mar. 3, 2025. cited by applicant

Miandad R et al. Effect of plastic waste types on pyrolysis liquid oil, *International Biodeterioration & Biodegradation*, vol. 119, Apr. 2017, pp. 239-252. cited by applicant

Miskolczi et al. Fuels by pyrolysis of waste plastics from agricultural and packaging sectors in a pilot scale reactor, *Fuel Processing Technology*, vol. 90, Issues 7-8, Jul.-Aug. 2009, pp. 1032-1040. cited by applicant

J. Schiers et al. *Feedstock Recycling and Pyrolysis of Waste Plastic: Converting Plastics into Diesel and Other Fuels*. 2006, John Wiley and Sons. cited by applicant

Cano Londono NA et al. Perspectives on circular economy in the context of chemical engineering and sustainable development, *Current Opinion in Chemical Engineering*, 2021, vol. 34, 100738. cited by applicant

Mass Balance Approach to Accelerate the Use of Renewable Feedstocks in Chemical Processes, *Plastics Europe*, Jan. 2020 (6 pages). cited by applicant

Safety Data Sheet for Crude Oil CAS-2068009-57-2; Oct. 7, 2020; 17 pages. cited by applicant

Dinkel et al., Question 60 publication, AFPM, 2017. cited by applicant

O'Reilly, *Defend Against Silicon Poisoning*, *Hydrocarbon Eng. Special Reports*, 2017. cited by applicant

Verdier, et al., *Hydroprocessing of Renewable Feedstocks—Challenges and Solutions*, Haldor Topsoe Whitepaper, Mar. 6, 2019. cited by applicant

Sundaram, K.M., Stancato, B., Lummus Technology, “How Much is Too Much?—Feed Contaminants and Their Consequences,” *AIChE 2018 Spring National Meeting Paper No. 32d*, 2018. cited by applicant

Kusenberg et al., “Challenges and Opportunities for Plastic Waste Pyrolysis Oils as Steam Cracking Feedstock,” *AIChE 2021 Spring National Meeting Paper No. 41a*, 2021. cited by applicant

“Shell uses plastic waste to produce chemicals.” Nov. 21, 2019, <https://www.shell.com/business-customers/chemicals/media-releases/2019-media-releases/shell-uses-plastic-waste-to-produce-chemicals.html>, accessed Jun. 20, 2024. cited by applicant

Chemical Recycling: Tackling Plastic Waste. Shell Chemicals is working to utilise plastic waste as feedstock in our global chemical plants. Date Unknown <https://www.shell.com/business-customers/chemicals/chemical-recycling-tackling-plastic-waste.html#iframe=L3dlYmFwcHMvU2h1bGxfQ2h1bWljYWxzX1JIY3ljbGluZy8=>. cited by applicant

Rezvani Ghomi, Erfan, et al. “The flame retardancy of polyethylene composites: from fundamental concepts to nanocomposites.” *Molecules* 25.21 (2020): 5157. <https://doi.org/10.3390/molecules25215157>. cited by applicant

Pan, Y. Q., et al. “Improved flame retardant of intumescent flame retardant flame-retarded high density polyethylene with fullerene decorated by iron compound.” *eXPRESS Polymer Letters* 13.9

(2019). <<https://doi.org/10.3144/expresspolymlett.2019.72>> (Year: 2019). cited by applicant

Deng, Cong, et al. "Effect of two types of iron MMTs on the flame retardation of LDPE composite." *Polymer degradation and stability* 103 (2014): 1-10.
<https://doi.org/10.1016/j.polymdegradstab.2014.03.001>. cited by applicant

Gary, J.H., et al., 2007, *Petroleum Refining Technology and Economics*, 5th ed., CRC Press, 465 pp. (Year: 2007). cited by applicant

Gary, JH et al. 2007, *Petroleum Refining Technology and Economics*, 5th ed. CRC Press, p. 463. cited by applicant

Carvalho, Bárbara O., et al. "Replacing harmful flame retardants with biodegradable starch-based materials in polyethylene formulations." *Polymers* 15.20 (2023): 4078. cited by applicant

International Search Report and Written Opinion mailed Aug. 28, 2024 in International Application No. PCT/ US24/21598 (15 pages). cited by applicant

Extended European Search Report mailed Oct. 8, 2024 in European Application No. 24167096.7 (8 pages). cited by applicant

Extended European Search Report mailed Oct. 4, 2024 in European Application No. 24167095.9 (8 pages). cited by applicant

Extended European Search Report mailed Oct. 8, 2024 in European Application No. 24167097.5 (7 pages). cited by applicant

Nexus and Shell sign strategic supply agreement to scale up commercial production of chemical from plastic waste Nov. 19, 2020. <https://www.shell.com/business-customers/chemicals/media-releases/2020-media-releases/nexus-and-shell-sign-strategic-supply-agreement-to-scale-up-commercial-production-of-chemicals-from-plastic-waste.html>. cited by applicant

Shell, YouTube, Plastic Waste to mChemicals, 2019.pdf. cited by applicant

Shell, Sustainability Report 2020. 13 pages. cited by applicant

Shell uses plastic waste to produce resin feedstocks, *Plastics Today*, Jan. 21, 2020, <https://www.plasticstoday.com/sustainability/shell-uses-plastic-waste-to-produce-resin-feedstocks>, Accessed Mar. 3, 2025. cited by applicant

The path to zero waste—the value of chemical recycling. Eastman. May 2023
<https://www.eastman.com/content/dam/eastman/corporate/en/literature/c/circrt12181.pdf>, Accessed Mar. 4, 2025. cited by applicant

Coleman B et al. LCA carbon footprint summary report for Eastman carbon renewal technology. Jun. 10, 2020. 12 pages. cited by applicant

Karanam S. The role of advanced recycling in closing the loop for plastics and circular economy. Mar. 9, 2020. 26 pages. cited by applicant

ChemCycling®: Creating a circular plastics economy with chemical recycling. BASF. Sep. 2024, <https://www.basf.com/us/en/who-we-are/sustainability/we-drive-sustainable-solutions/circular-economy/mass-balance-approach/chemcycling>; accessed Mar. 4, 2025. cited by applicant

Chemical Recycling: Accelerating Circularity. BASF. Apr. 20, 2023, 5 pages. cited by applicant

Sharuddin SDA et al. A review on pyrolysis of plastic wastes. *Energy Conversion and Management*, vol. 115, May 1, 2016, pp. 308-326. cited by applicant

Thibodeaux A. Plastic waste is new resource for Shell Norco, Jan. 24, 2020.
<https://www.heraldguide.com/featured/plastic-waste-is-new-resource-for-shell-norco/>; Accessed Mar. 4, 2025. cited by applicant

SABIC Mass Balance. Sep. 11, 2019. <https://www.youtube.com/watch?v=-imvDD6i6Lo>; Accessed Mar. 4, 2025. cited by applicant

Sharma, B. et al. Production, characterization and fuel properties of alternative diesel fuel from pyrolysis of waste plastic grocery bags. *Fuel Processing Technology*, vol. 122, Jun. 2014, pp. 79-90. cited by applicant

Khan et al. Pyrolytic waste plastic oil and its diesel blend: fuel characterization. *Journal of Environmental and Public Health*, vol. 2016, Jun. 5, 2016. cited by applicant

Primary Examiner: McCaig; Brian A

Attorney, Agent or Firm: Meunier Carlin & Curfman LLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application claims the benefit of priority to U.S. Provisional Application No. 63/626,488, filed Jan. 29, 2024, which is incorporated by reference herein in its entirety.

BACKGROUND

(1) Single use plastic waste is a pressing environmental issue. There are currently few options for recycling a mixed polyolefin stream comprised of a broad range of compositions and physical forms of polyethylene, polypropylene, and polystyrene waste plastics to value-added chemical and refinery feedstock products. Improved processes are needed for recycling such plastics at an industrially significant scale and for producing improved products therefrom. The compositions and methods discussed herein address these and other needs.

SUMMARY

(2) In accordance with the purposes of the disclosed compositions and methods as embodied and broadly described herein, the disclosed subject matter relates to hydrocarbon-based compositions derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics and methods of making and use thereof.

(3) Disclosed herein is a method for pyrolysis of plastic feedstock comprising post-consumer and/or post-industrial plastics. In various implementations, the method may comprise directing the plastic feedstock into an internal volume of a reactor vessel, and pyrolyzing the plastic feedstock in the internal volume of the reactor vessel. In certain implementations, the step of pyrolyzing the plastic feedstock may comprise using one or more heaters to heat the plastic feedstock in the reactor vessel's internal volume to a temperature of 200° C. or more, and using the one or more heaters to apply energy at a combined energy density between 0.05 and 0.7 kW per pound of pyrolyzed product produced within the reactor.

(4) Additional advantages of the disclosed compositions and methods will be set forth in part in the description which follows, and in part will be obvious from the description. The advantages of the disclosed compositions and methods will be realized and attained by means of the elements and combinations particularly pointed out in the appended claims. It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the disclosed systems and methods, as claimed.

(5) The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the invention will be apparent from the description and drawings, and from the claims.

Description

BRIEF DESCRIPTION OF THE FIGURES

- (1) The accompanying figures, which are incorporated in and constitute a part of this specification, illustrate several aspects of the disclosure, and together with the description, serve to explain the principles of the disclosure.
- (2) FIG. 1. Schematic diagram of an example system and/or method as disclosed herein according to one implementation.
- (3) FIG. 2. Schematic diagram of an example system and/or method as disclosed herein according to one implementation.
- (4) FIG. 3. Schematic diagram of an example system and/or method as disclosed herein according to one implementation.
- (5) FIG. 4. Schematic diagram of an example system and/or method as disclosed herein according to one implementation.
- (6) FIG. 5. Schematic diagram of an example system and/or method as disclosed herein according to one implementation.
- (7) FIG. 6. UV-Vis spectrum of wax product in hexane with a 100× dilution factor.
- (8) FIG. 7. UV-Vis spectrum of wax product in hexane with a 1,000× dilution factor.
- (9) FIG. 8. FTIR-ATR spectrum of wax product.
- (10) FIG. 9. Gas chromatogram of wax product.
- (11) FIG. 10. Gas chromatogram of wax product.
- (12) FIG. 11. ¹H-NMR spectrum of wax product.
- (13) FIG. 12. ¹H-NMR spectrum of wax product with annotations.
- (14) FIG. 13. ¹³C-NMR spectrum of wax product.
- (15) FIG. 14. ¹³C-NMR spectrum of wax product with annotations.
- (16) FIG. 15. UV-Vis spectrum of oil product in hexane with a 100× dilution factor.
- (17) FIG. 16. UV-Vis spectrum of oil product in hexane with a 1,000× dilution factor.
- (18) FIG. 17. FTIR-ATR spectrum of oil product.
- (19) FIG. 18. GC-FID chromatogram of oil product.
- (20) FIG. 19. GC-FID chromatogram of oil product.
- (21) FIG. 20. ¹H-NMR spectrum of oil product.
- (22) FIG. 21. ¹H-NMR spectrum of oil product with annotations.
- (23) FIG. 22. ¹³C-NMR spectrum of oil product.
- (24) FIG. 23. ¹³C-NMR spectrum of oil product with annotations.
- (25) FIG. 24. Schematic perspective side view of an example single-screw extruder with an electrically heated barrel.
- (26) FIG. 25. Cross-sectional view of the example single-screw extruder of FIG. 24.
- (27) FIG. 26. Schematic perspective side view of an example dual-screw extruder with an electrically heated barrel.
- (28) FIG. 27. Cross-sectional view of the example dual-screw extruder of FIG. 26.
- (29) FIG. 28. Schematic perspective side view of an example single-screw extruder with a gas/flame heated barrel.
- (30) FIG. 29. Schematic perspective side view of an example single-screw extruder with an oil heated barrel.
- (31) FIG. 30. Schematic perspective side view of an example single-screw extruder with an electrically heated barrel and a single vent.
- (32) FIG. 31. Schematic perspective side view of an example single-screw extruder with an electrically heated barrel and two vents.
- (33) FIG. 32. Schematic perspective side view of an example single-screw extruder with an electrically heated barrel and four vents.
- (34) FIG. 33. Schematic perspective side view of an example single-screw extruder with an

electrically heated barrel, two vents, and a vent stuffer.

(35) FIG. 34. Schematic perspective front view of an example vent stuffer.

(36) FIG. 35. Schematic side view of an example rotary kiln reactor.

(37) FIG. 36. Schematic top view of the example rotary kiln reactor of FIG. 35.

(38) FIG. 37. Schematic side view of an example screw reactor.

(39) FIG. 38. Schematic top view of the example screw reactor of FIG. 37.

(40) FIG. 39. Schematic side view of an example fluidized bed reactor.

(41) FIG. 40. Schematic top view of the example fluidized bed reactor of FIG. 39.

(42) FIG. 41. Schematic side view of an example batch reactor.

(43) FIG. 42. Schematic top view of the example batch reactor of FIG. 41.

(44) FIG. 43. Schematic side view of an example continuously stirred reactor with external gas heating.

(45) FIG. 44. Schematic top view of the example continuously stirred reactor of FIG. 43.

(46) FIG. 45. Schematic side view of an example continuously stirred reactor with external gas heating and internal electric heating.

(47) FIG. 46. Schematic top view of the example continuously stirred reactor of FIG. 45.

(48) FIG. 47. Schematic side view of an example continuously stirred reactor with external electrical heating and internal electric heating.

(49) FIG. 48. Schematic top view of the example continuously stirred reactor of FIG. 47.

(50) FIG. 49. Schematic side view of an example molten material reactor.

DETAILED DESCRIPTION

(51) The compositions, methods, and systems described herein may be understood more readily by reference to the following detailed description of specific aspects of the disclosed subject matter and the Examples included therein.

(52) Before the present compositions, methods, and systems are disclosed and described, it is to be understood that the aspects described below are not limited to specific synthetic methods or specific reagents, as such may, of course, vary. It is also to be understood that the terminology used herein is for the purpose of describing particular aspects only and is not intended to be limiting.

(53) Also, throughout this specification, various publications are referenced. The disclosures of these publications in their entireties are hereby incorporated by reference into this application in order to more fully describe the state of the art to which the disclosed matter pertains. The references disclosed are also individually and specifically incorporated by reference herein for the material contained in them that is discussed in the sentence in which the reference is relied upon.

(54) General Definitions

(55) In this specification and in the claims that follow, reference will be made to a number of terms, which shall be defined to have the following meanings.

(56) Throughout the description and claims of this specification, the word “comprise” and other forms of the word, such as “comprising” and “comprises,” means including but not limited to, and is not intended to exclude, for example, other additives, components, integers, or steps.

(57) As used in the description and the appended claims, the singular forms “a,” “an,” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to “a composition” includes mixtures of two or more such compositions, reference to “an agent” includes mixtures of two or more such agents, reference to “the component” includes mixtures of two or more such components, and the like.

(58) “Optional” or “optionally” means that the subsequently described event or circumstance can or cannot occur, and that the description includes instances where the event or circumstance occurs and instances where it does not.

(59) Ranges can be expressed herein as from “about” one particular value, and/or to “about” another particular value. By “about” is meant within 5% of the value, e.g., within 4, 3, 2, or 1% of the value. When such a range is expressed, another aspect includes from the one particular value

and/or to the other particular value. Similarly, when values are expressed as approximations, by use of the antecedent “about,” it will be understood that the particular value forms another aspect. It will be further understood that the endpoints of each of the ranges are significant both in relation to the other endpoint, and independently of the other endpoint.

(60) Values can be expressed herein as an “average” value. “Average” generally refers to the statistical mean value.

(61) By “substantially” is meant within 5%, e.g., within 4%, 3%, 2%, or 1%.

(62) “Exemplary” means “an example of” and is not intended to convey an indication of a preferred or ideal embodiment. “Such as” is not used in a restrictive sense, but for explanatory purposes.

(63) It is understood that throughout this specification the identifiers “first” and “second” are used solely to aid in distinguishing the various components and steps of the disclosed subject matter. The identifiers “first” and “second” are not intended to imply any particular order, amount, preference, or importance to the components or steps modified by these terms.

(64) References in the specification and concluding claims to parts by weight of a particular element or component in a composition denotes the weight relationship between the element or component and any other elements or components in the composition or article for which a part by weight is expressed. Thus, in a compound containing 2 parts by weight of component X and 5 parts by weight component Y, X and Y are present at a weight ratio of 2:5, and are present in such ratio regardless of whether additional components are contained in the compound.

(65) A weight percent (wt. %) of a component, unless specifically stated to the contrary, is based on the total weight of the formulation or composition in which the component is included.

(66) The term “or combinations thereof” as used herein refers to all permutations and combinations of the listed items preceding the term. For example, “A, B, C, or combinations thereof” is intended to include at least one of: A, B, C, AB, AC, BC, or ABC, and if order is important in a particular context, also BA, CA, CB, CBA, BCA, ACB, BAC, or CAB.

(67) Continuing with this example, expressly included are combinations that contain repeats of one or more item or term, such as BB, AAA, AB, BBC, AAABCCCC, CBBAAA, CABABB, and so forth. The skilled artisan will understand that typically there is no limit on the number of items or terms in any combination, unless otherwise apparent from the context.

(68) Chemical Definitions

(69) Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs.

(70) The organic moieties mentioned when defining variable positions within the general formulae described herein (e.g., the term “halogen”) are collective terms for the individual substituents encompassed by the organic moiety. The prefix Cn-Cm preceding a group or moiety indicates, in each case, the possible number of carbon atoms in the group or moiety that follows.

(71) The term “ion,” as used herein, refers to any molecule, portion of a molecule, cluster of molecules, molecular complex, moiety, or atom that contains a charge (positive, negative, or both at the same time within one molecule, cluster of molecules, molecular complex, or moiety (e.g., zwitterions)) or that can be made to contain a charge. Methods for producing a charge in a molecule, portion of a molecule, cluster of molecules, molecular complex, moiety, or atom are disclosed herein and can be accomplished by methods known in the art, e.g., protonation, deprotonation, oxidation, reduction, alkylation, acetylation, esterification, de-esterification, hydrolysis, etc.

(72) The term “anion” is a type of ion and is included within the meaning of the term “ion.” An “anion” is any molecule, portion of a molecule (e.g., zwitterion), cluster of molecules, molecular complex, moiety, or atom that contains a net negative charge or that can be made to contain a net negative charge. The term “anion precursor” is used herein to specifically refer to a molecule that can be converted to an anion via a chemical reaction (e.g., deprotonation).

(73) The term “cation” is a type of ion and is included within the meaning of the term “ion.” A

“cation” is any molecule, portion of a molecule (e.g., zwitterion), cluster of molecules, molecular complex, moiety, or atom, that contains a net positive charge or that can be made to contain a net positive charge. The term “cation precursor” is used herein to specifically refer to a molecule that can be converted to a cation via a chemical reaction (e.g., protonation or alkylation).

(74) As used herein, the term “substituted” is contemplated to include all permissible substituents of organic compounds. In a broad aspect, the permissible substituents include acyclic and cyclic, branched and unbranched, carbocyclic and heterocyclic, and aromatic and nonaromatic substituents of organic compounds. Illustrative substituents include, for example, those described below. The permissible substituents can be one or more and the same or different for appropriate organic compounds. For purposes of this disclosure, the heteroatoms, such as nitrogen, can have hydrogen substituents and/or any permissible substituents of organic compounds described herein which satisfy the valencies of the heteroatoms. This disclosure is not intended to be limited in any manner by the permissible substituents of organic compounds. Also, the terms “substitution” or “substituted with” include the implicit proviso that such substitution is in accordance with permitted valence of the substituted atom and the substituent, and that the substitution results in a stable compound, e.g., a compound that does not spontaneously undergo transformation such as by rearrangement, cyclization, elimination, etc.

(75) “Z.sup.1,” “Z.sup.2,” “Z.sup.3,” and “Z.sup.4” are used herein as generic symbols to represent various specific substituents. These symbols can be any substituent, not limited to those disclosed herein, and when they are defined to be certain substituents in one instance, they can, in another instance, be defined as some other substituents.

(76) The term “aliphatic” as used herein refers to a non-aromatic hydrocarbon group and includes branched and unbranched, alkyl, alkenyl, or alkynyl groups.

(77) As used herein, the term “alkyl” refers to saturated, straight-chained or branched saturated hydrocarbon moieties. Unless otherwise specified, C.sub.1-C.sub.24 (e.g., C.sub.1-C.sub.22, C.sub.1-C.sub.20, C.sub.1-C.sub.15, C.sub.1-C.sub.16, C.sub.1-C.sub.14, C.sub.1-C.sub.12, C.sub.1-C.sub.10, C.sub.1-C.sub.8, C.sub.1-C.sub.6, or C.sub.1-C.sub.4) alkyl groups are intended. Examples of alkyl groups include methyl, ethyl, propyl, 1-methyl-ethyl, butyl, 1-methyl-propyl, 2-methyl-propyl, 1,1-dimethyl-ethyl, pentyl, 1-methyl-butyl, 2-methyl-butyl, 3-methyl-butyl, 2,2-dimethyl-propyl, 1-ethyl-propyl, hexyl, 1,1-dimethyl-propyl, 1,2-dimethyl-propyl, 1-methyl-pentyl, 2-methyl-pentyl, 3-methyl-pentyl, 4-methyl-pentyl, 1,1-dimethyl-butyl, 1,2-dimethyl-butyl, 1,3-dimethyl-butyl, 2,2-dimethyl-butyl, 2,3-dimethyl-butyl, 3,3-dimethyl-butyl, 1-ethyl-butyl, 2-ethyl-butyl, 1,1,2-trimethyl-propyl, 1,2,2-trimethyl-propyl, 1-ethyl-1-methyl-propyl, 1-ethyl-2-methyl-propyl, heptyl, octyl, nonyl, decyl, dodecyl, tetradecyl, hexadecyl, eicosyl, tetracosyl, and the like. Alkyl substituents may be unsubstituted or substituted with one or more chemical moieties. The alkyl group can be substituted with one or more groups including, but not limited to, hydroxyl, halogen, acyl, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, aldehyde, amino, cyano, carboxylic acid, ester, ether, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol, as described below, provided that the substituents are sterically compatible and the rules of chemical bonding and strain energy are satisfied.

(78) Throughout the specification “alkyl” is generally used to refer to both unsubstituted alkyl groups and substituted alkyl groups; however, substituted alkyl groups are also specifically referred to herein by identifying the specific substituent(s) on the alkyl group. For example, the term “halogenated alkyl” specifically refers to an alkyl group that is substituted with one or more halides (halogens; e.g., fluorine, chlorine, bromine, or iodine). The term “alkoxyalkyl” specifically refers to an alkyl group that is substituted with one or more alkoxy groups, as described below. The term “alkylamino” specifically refers to an alkyl group that is substituted with one or more amino groups, as described below, and the like. When “alkyl” is used in one instance and a specific term such as “alkylalcohol” is used in another, it is not meant to imply that the term “alkyl” does not also refer to specific terms such as “alkylalcohol” and the like.

(79) This practice is also used for other groups described herein. That is, while a term such as “cycloalkyl” refers to both unsubstituted and substituted cycloalkyl moieties, the substituted moieties can, in addition, be specifically identified herein; for example, a particular substituted cycloalkyl can be referred to as, e.g., an “alkylcycloalkyl.” Similarly, a substituted alkoxy can be specifically referred to as, e.g., a “halogenated alkoxy,” a particular substituted alkenyl can be, e.g., an “alkenylalcohol,” and the like. Again, the practice of using a general term, such as “cycloalkyl,” and a specific term, such as “alkylcycloalkyl,” is not meant to imply that the general term does not also include the specific term.

(80) As used herein, the term “alkenyl” refers to unsaturated, straight-chained, or branched hydrocarbon moieties containing a double bond. Unless otherwise specified, C.sub.2-C.sub.24 (e.g., C.sub.2-C.sub.22, C.sub.2-C.sub.20, C.sub.2-C.sub.18, C.sub.2-C.sub.16, C.sub.2-C.sub.14, C.sub.2-C.sub.12, C.sub.2-C.sub.10, C.sub.2-C.sub.8, C.sub.2-C.sub.6, or C.sub.2-C.sub.4) alkenyl groups are intended. Alkenyl groups may contain more than one unsaturated bond. Examples include ethenyl, 1-propenyl, 2-propenyl, 1-methylethenyl, 1-butenyl, 2-butenyl, 3-butenyl, 1-methyl-1-propenyl, 2-methyl-1-propenyl, 1-methyl-2-propenyl, 2-methyl-2-propenyl, 1-pentenyl, 2-pentenyl, 3-pentenyl, 4-pentenyl, 1-methyl-1-butenyl, 2-methyl-1-butenyl, 3-methyl-1-butenyl, 1-methyl-2-butenyl, 2-methyl-2-butenyl, 3-methyl-2-butenyl, 1-methyl-3-butenyl, 2-methyl-3-butenyl, 3-methyl-3-butenyl, 1,1-dimethyl-2-propenyl, 1,2-dimethyl-1-propenyl, 1,2-dimethyl-2-propenyl, 1-ethyl-1-propenyl, 1-ethyl-2-propenyl, 1-hexenyl, 2-hexenyl, 3-hexenyl, 4-hexenyl, 5-hexenyl, 1-methyl-1-pentenyl, 2-methyl-1-pentenyl, 3-methyl-1-pentenyl, 4-methyl-1-pentenyl, 1-methyl-2-pentenyl, 2-methyl-2-pentenyl, 3-methyl-2-pentenyl, 4-methyl-2-pentenyl, 1-methyl-3-pentenyl, 2-methyl-3-pentenyl, 3-methyl-3-pentenyl, 4-methyl-3-pentenyl, 1-methyl-4-pentenyl, 2-methyl-4-pentenyl, 3-methyl-4-pentenyl, 4-methyl-4-pentenyl, 1,1-dimethyl-2-butenyl, 1,1-dimethyl-3-butenyl, 1,2-dimethyl-1-butenyl, 1,2-dimethyl-2-butenyl, 1,2-dimethyl-3-butenyl, 1,3-dimethyl-1-butenyl, 1,3-dimethyl-2-butenyl, 1,3-dimethyl-3-butenyl, 2,2-dimethyl-3-butenyl, 2,3-dimethyl-1-butenyl, 2,3-dimethyl-2-butenyl, 2,3-dimethyl-3-butenyl, 3,3-dimethyl-1-butenyl, 3,3-dimethyl-2-butenyl, 1-ethyl-1-butenyl, 1-ethyl-2-butenyl, 1-ethyl-3-butenyl, 2-ethyl-1-butenyl, 2-ethyl-2-butenyl, 2-ethyl-3-butenyl, 1,1,2-trimethyl-2-propenyl, 1-ethyl-1-methyl-2-propenyl, 1-ethyl-2-methyl-1-propenyl, and 1-ethyl-2-methyl-2-propenyl. The term “vinyl” refers to a group having the structure —CH=CH.sub.2; 1-propenyl refers to a group with the structure —CH=CH—CH.sub.3; and 2-propenyl refers to a group with the structure —CH.sub.2—CH=CH.sub.2.

Asymmetric structures such as (Z.sup.1Z.sup.2)C=C(Z.sup.3Z.sup.4) are intended to include both the E and Z isomers. This can be presumed in structural formulae herein wherein an asymmetric alkene is present, or it can be explicitly indicated by the bond symbol C=C. Alkenyl substituents may be unsubstituted or substituted with one or more chemical moieties. Examples of suitable substituents include, for example, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, acyl, aldehyde, amino, cyano, carboxylic acid, ester, ether, halide, hydroxyl, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol, as described below, provided that the substituents are sterically compatible and the rules of chemical bonding and strain energy are satisfied.

(81) As used herein, the term “alkynyl” represents straight-chained or branched hydrocarbon moieties containing a triple bond. Unless otherwise specified, C.sub.2-C.sub.24 (e.g., C.sub.2-C.sub.24, C.sub.2-C.sub.20, C.sub.2-C.sub.18, C.sub.2-C.sub.16, C.sub.2-C.sub.14, C.sub.2-C.sub.12, C.sub.2-C.sub.10, C.sub.2-C.sub.8, C.sub.2-C.sub.6, or C.sub.2-C.sub.4) alkynyl groups are intended. Alkynyl groups may contain more than one unsaturated bond. Examples include C.sub.2-C.sub.6-alkynyl, such as ethynyl, 1-propynyl, 2-propynyl (or propargyl), 1-butyne, 2-butyne, 3-butyne, 1-methyl-2-propynyl, 1-pentyne, 2-pentyne, 3-pentyne, 4-pentyne, 3-methyl-1-butyne, 1-methyl-2-butyne, 1-methyl-3-butyne, 2-methyl-3-butyne, 1,1-dimethyl-2-propynyl, 1-ethyl-2-propynyl, 1-hexynyl, 2-hexynyl, 3-hexynyl, 4-hexynyl, 5-hexynyl, 3-methyl-1-pentyne, 4-methyl-1-pentyne, 1-methyl-2-pentyne, 4-methyl-2-pentyne, 1-methyl-3-pentyne, 2-methyl-3-pentyne, 1-methyl-4-pentyne, 2-methyl-4-pentyne, 3-methyl-4-pentyne, 1,1-

dimethyl-2-butynyl, 1,1-dimethyl-3-butynyl, 1,2-dimethyl-3-butynyl, 2,2-dimethyl-3-butynyl, 3,3-dimethyl-1-butynyl, 1-ethyl-2-butynyl, 1-ethyl-3-butynyl, 2-ethyl-3-butynyl, and 1-ethyl-1-methyl-2-propynyl. Alkynyl substituents may be unsubstituted or substituted with one or more chemical moieties. Examples of suitable substituents include, for example, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, acyl, aldehyde, amino, cyano, carboxylic acid, ester, ether, halide, hydroxyl, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol, as described below.

(82) As used herein, the term “aryl,” as well as derivative terms such as aryloxy, refers to groups that include a monovalent aromatic carbocyclic group of from 3 to 50 carbon atoms. Aryl groups can include a single ring or multiple condensed rings. In some examples, aryl groups include C.sub.6-C.sub.10 aryl groups. Examples of aryl groups include, but are not limited to, benzene, phenyl, biphenyl, naphthyl, tetrahydronaphthyl, phenylcyclopropyl, phenoxybenzene, and indanyl. The term “aryl” also includes “heteroaryl,” which is defined as a group that contains an aromatic group that has at least one heteroatom incorporated within the ring of the aromatic group. Examples of heteroatoms include, but are not limited to, nitrogen, oxygen, sulfur, and phosphorus. The term “non-heteroaryl,” which is also included in the term “aryl,” defines a group that contains an aromatic group that does not contain a heteroatom. The aryl substituents may be unsubstituted or substituted with one or more chemical moieties. Examples of suitable substituents include, for example, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, acyl, aldehyde, amino, cyano, carboxylic acid, ester, ether, halide, hydroxyl, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol as described herein. The term “biaryl” is a specific type of aryl group and is included in the definition of aryl. Biaryl refers to two aryl groups that are bound together via a fused ring structure, as in naphthalene, or are attached via one or more carbon-carbon bonds, as in biphenyl.

(83) The term “cycloalkyl” as used herein is a non-aromatic carbon-based ring composed of at least three carbon atoms. Examples of cycloalkyl groups include, but are not limited to, cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, etc. The term “heterocycloalkyl” is a cycloalkyl group as defined above where at least one of the carbon atoms of the ring is substituted with a heteroatom such as, but not limited to, nitrogen, oxygen, sulfur, or phosphorus. The cycloalkyl group and heterocycloalkyl group can be substituted or unsubstituted. The cycloalkyl group and heterocycloalkyl group can be substituted with one or more groups including, but not limited to, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, acyl, aldehyde, amino, cyano, carboxylic acid, ester, ether, halide, hydroxyl, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol as described herein.

(84) The term “cycloalkenyl” as used herein is a non-aromatic carbon-based ring composed of at least three carbon atoms and containing at least one double bond, i.e., C=C. Examples of cycloalkenyl groups include, but are not limited to, cyclopropenyl, cyclobutenyl, cyclopentenyl, cyclopentadienyl, cyclohexenyl, cyclohexadienyl, and the like. The term “heterocycloalkenyl” is a type of cycloalkenyl group as defined above and is included within the meaning of the term “cycloalkenyl,” where at least one of the carbon atoms of the ring is substituted with a heteroatom such as, but not limited to, nitrogen, oxygen, sulfur, or phosphorus. The cycloalkenyl group and heterocycloalkenyl group can be substituted or unsubstituted. The cycloalkenyl group and heterocycloalkenyl group can be substituted with one or more groups including, but not limited to, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, acyl, aldehyde, amino, cyano, carboxylic acid, ester, ether, halide, hydroxyl, ketone, nitro, phosphonyl, silyl, sulfo-oxo, sulfonyl, sulfone, sulfoxide, or thiol as described herein.

(85) The term “cyclic group” is used herein to refer to either aryl groups, non-aryl groups (i.e., cycloalkyl, heterocycloalkyl, cycloalkenyl, and heterocycloalkenyl groups), or both. Cyclic groups have one or more ring systems (e.g., monocyclic, bicyclic, tricyclic, polycyclic, etc.) that can be substituted or unsubstituted. A cyclic group can contain one or more aryl groups, one or more non-aryl groups, or one or more aryl groups and one or more non-aryl groups.

- (86) The term “acyl” as used herein is represented by the formula $\text{—C(O)Z}^{\text{sup.1}}$ where $\text{Z}^{\text{sup.1}}$ can be a hydrogen, hydroxyl, alkoxy, alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above. As used herein, the term “acyl” can be used interchangeably with “carbonyl.” Throughout this specification “C(O)” or “CO” is a shorthand notation for C=O .
- (87) The term “acetal” as used herein is represented by the formula $(\text{Z}^{\text{sup.1}}\text{Z}^{\text{sup.2}})\text{C(=OZ}^{\text{sup.3}})(=\text{OZ}^{\text{sup.4}})$, where $\text{Z}^{\text{sup.1}}$, $\text{Z}^{\text{sup.2}}$, $\text{Z}^{\text{sup.3}}$, and $\text{Z}^{\text{sup.4}}$ can be, independently, a hydrogen, halogen, hydroxyl, alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (88) The term “alkanol” as used herein is represented by the formula $\text{Z}^{\text{sup.1}}\text{OH}$, where $\text{Z}^{\text{sup.1}}$ can be an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (89) As used herein, the term “alkoxy” as used herein is an alkyl group bound through a single, terminal ether linkage; that is, an “alkoxy” group can be defined as to a group of the formula $\text{Z}^{\text{sup.1}}\text{—O—}$, where $\text{Z}^{\text{sup.1}}$ is unsubstituted or substituted alkyl as defined above. Unless otherwise specified, alkoxy groups wherein $\text{Z}^{\text{sup.1}}$ is a $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.24}}$ (e.g., $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.22}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.20}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.15}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.16}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.14}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.12}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.10}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.8}}$, $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.6}}$, or $\text{C}^{\text{sub.1}}\text{—C}^{\text{sub.4}}$) alkyl group are intended. Examples include methoxy, ethoxy, propoxy, 1-methyl-ethoxy, butoxy, 1-methyl-propoxy, 2-methyl-propoxy, 1,1-dimethyl-ethoxy, pentoxy, 1-methyl-butyloxy, 2-methyl-butoxy, 3-methyl-butoxy, 2,2-di-methyl-propoxy, 1-ethyl-propoxy, hexoxy, 1,1-dimethyl-propoxy, 1,2-dimethyl-propoxy, 1-methyl-pentoxy, 2-methyl-pentoxy, 3-methyl-pentoxy, 4-methyl-pentoxy, 1,1-dimethyl-butoxy, 1,2-dimethyl-butoxy, 1,3-dimethyl-butoxy, 2,2-dimethyl-butoxy, 2,3-dimethyl-butoxy, 3,3-dimethyl-butoxy, 1-ethyl-butoxy, 2-ethylbutoxy, 1,1,2-trimethyl-propoxy, 1,2,2-trimethyl-propoxy, 1-ethyl-1-methyl-propoxy, and 1-ethyl-2-methyl-propoxy.
- (90) The term “aldehyde” as used herein is represented by the formula —C(O)H .
- (91) Throughout this specification “C(O)” is a shorthand notation for C=O .
- (92) The term “amino” as used herein are represented by the formula $\text{—NZ}^{\text{sup.1}}\text{Z}^{\text{sup.2}}\text{Z}^{\text{sup.3}}$, where $\text{Z}^{\text{sup.1}}$, $\text{Z}^{\text{sup.2}}$, and $\text{Z}^{\text{sup.3}}$ can each be substitution group as described herein, such as hydrogen, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (93) The terms “amide” or “amido” as used herein are represented by the formula $\text{—C(O)NZ}^{\text{sup.1}}\text{Z}^{\text{sup.2}}$, where $\text{Z}^{\text{sup.1}}$ and $\text{Z}^{\text{sup.2}}$ can each be substitution group as described herein, such as hydrogen, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (94) The term “anhydride” as used herein is represented by the formula $\text{Z}^{\text{sup.1}}\text{C(O)OC(O)Z}^{\text{sup.2}}$ where $\text{Z}^{\text{sup.1}}$ and $\text{Z}^{\text{sup.2}}$, independently, can be an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (95) The term “cyclic anhydride” as used herein is represented by the formula:
- (96) ##STR00001## where $\text{Z}^{\text{sup.1}}$ can be an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (97) The term “azide” as used herein is represented by the formula —N=N=N .
- (98) The term “carboxylic acid” as used herein is represented by the formula —C(O)OH .
- (99) A “carboxylate” or “carboxyl” group as used herein is represented by the formula $\text{—C(O)O}^{\text{sup.1}}$.
- (100) The term “cyano” as used herein is represented by the formula —CN .
- (101) The term “ester” as used herein is represented by the formula $\text{—OC(O)Z}^{\text{sup.1}}$ or $\text{—C(O)OZ}^{\text{sup.1}}$, where $\text{Z}^{\text{sup.1}}$ can be an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.
- (102) The term “ether” as used herein is represented by the formula $\text{Z}^{\text{sup.1}}\text{OZ}^{\text{sup.2}}$, where

Z.sup.1 and Z.sup.2 can be, independently, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(103) The term “epoxy” or “epoxide” as used herein refers to a cyclic ether with a three atom ring and can be represented by the formula:

(104) ##STR00002##

where Z.sup.1, Z.sup.2, Z.sup.3, and Z.sup.4 can be, independently, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(105) The term “ketone” as used herein is represented by the formula Z.sup.1C(O)Z.sup.2, where Z.sup.1 and Z.sup.2 can be, independently, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(106) The term “halide” or “halogen” or “halo” as used herein refers to fluorine, chlorine, bromine, and iodine.

(107) The term “hydroxyl” as used herein is represented by the formula —OH.

(108) The term “nitro” as used herein is represented by the formula —NO.sub.2.

(109) The term “phosphonyl” is used herein to refer to the phospho-oxo group represented by the formula —P(O)(OZ.sup.1).sub.2, where Z.sup.1 can be hydrogen, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(110) The term “silyl” as used herein is represented by the formula —SiZ.sup.1Z.sup.2Z.sup.3, where Z.sup.1, Z.sup.2, and Z.sup.3 can be, independently, hydrogen, alkyl, alkoxy, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(111) The term “sulfonyl” or “sulfone” is used herein to refer to the sulfo-oxo group represented by the formula —S(O).sub.2Z.sup.1, where Z.sup.1 can be hydrogen, an alkyl, alkenyl, alkynyl, aryl, heteroaryl, cycloalkyl, cycloalkenyl, heterocycloalkyl, or heterocycloalkenyl group described above.

(112) The term “sulfide” as used herein comprises the formula —S—.

(113) The term “thiol” as used herein is represented by the formula —SH.

(114) “R.sup.1,” “R.sup.2,” “R.sup.2,” “R.sup.n,” etc., where n is some integer, as used herein can, independently, possess one or more of the groups listed above. For example, if R.sup.1 is a straight chain alkyl group, one of the hydrogen atoms of the alkyl group can optionally be substituted with a hydroxyl group, an alkoxy group, an amino group, an alkyl group, a halide, and the like.

Depending upon the groups that are selected, a first group can be incorporated within a second group or, alternatively, the first group can be pendant (i.e., attached) to the second group. For example, with the phrase “an alkyl group comprising an amino group,” the amino group can be incorporated within the backbone of the alkyl group. Alternatively, the amino group can be attached to the backbone of the alkyl group. The nature of the group(s) that is (are) selected will determine if the first group is embedded or attached to the second group.

(115) Unless stated to the contrary, a formula with chemical bonds shown only as solid lines and not as wedges or dashed lines contemplates each possible stereoisomer or mixture of stereoisomer (e.g., each enantiomer, each diastereomer, each meso compound, a racemic mixture, or scalemic mixture).

(116) Compositions

(117) Disclosed herein are hydrocarbon-based compositions derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics. Pyrolysis depolymerizes plastics into products comprised of building block molecules. Contaminants are introduced during plastic formulation and manufacturing processes during the first life of plastic in conjunction with the source and collection method of the plastics. Recycling of plastics via pyrolysis is a technology that generates products with a broad range of quality dependent upon a variety of factors, including the

feedstock and manufacturing process.

(118) "Post-industrial" or "Pre-consumer" plastics include materials derived from waste streams during a plastic manufacturing process.

(119) "Post-consumer" plastics include materials generated by households or by commercial, industrial, and/or institutional facilities in their roles as end-users of the product which can no longer be used for its intended purpose. This includes returns of material from the distribution chain.

(120) Sources of post-consumer and/or post-industrial plastics include, but are not limited to, plastic resin producers; packaging converters; industrial, commercial, retail, and institutional facilities; households; and waste collectors.

(121) In some examples, the compositions disclosed herein can comprise a wax, an oil, or a combination thereof.

(122) Wax

(123) For example, disclosed herein are waxes derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics. In some examples, the wax can be produced via pyrolysis at an industrial scale.

(124) The wax can, for example, have a number average molecular weight and/or a weight average molecular weight of 300 Daltons or more (e.g., 305 Daltons or more, 310 Daltons or more, 315 Daltons or more, 320 Daltons or more, 325 Daltons or more, 330 Daltons or more, 335 Daltons or more, 340 Daltons or more, 345 Daltons or more, 350 Daltons or more, 355 Daltons or more, 360 Daltons or more, 365 Daltons or more, 370 Daltons or more, 375 Daltons or more, 380 Daltons or more, 385 Daltons or more, or 390 Daltons or more). In some examples, the wax can have a number average molecular weight and/or a weight average molecular weight of 400 Daltons or less (e.g., 395 Daltons or less, 390 Daltons or less, 385 Daltons or less, 380 Daltons or less, 375 Daltons or less, 370 Daltons or less, 365 Daltons or less, 360 Daltons or less, 355 Daltons or less, 350 Daltons or less, 345 Daltons or less, 340 Daltons or less, 335 Daltons or less, 330 Daltons or less, 325 Daltons or less, 320 Daltons or less, 315 Daltons or less, or 310 Daltons or less). The number average molecular weight and/or weight average molecular weight of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a number average molecular weight and/or a weight average molecular weight of from 300 to 400 Daltons (e.g., from 300 to 350 Daltons, from 350 to 400 Daltons, from 300 to 320 Daltons, from 320 to 340 Daltons, from 340 to 360 Daltons, from 360 to 380 Daltons, from 380 to 400 Daltons, from 300 to 380 Daltons, from 300 to 360 Daltons, from 300 to 340 Daltons, from 320 to 400 Daltons, from 340 to 400 Daltons, from 360 to 400 Daltons, from 310 to 390 Daltons, from 320 to 380 Daltons, from 325 to 375 Daltons, or from 325 to 350 Daltons).

(125) The wax comprises a mixture of different hydrocarbons (e.g., linear, branched, cyclic, acyclic, saturated, unsaturated, aromatic, non-aromatic, etc.), any of which can optionally be substituted. In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 60% or more of the mixture (w/w) comprises C.sub.20-C.sub.45 hydrocarbons (e.g., 61% or more, 62% or more, 63% or more, 64% or more, 65% or more, 66% or more, 67% or more, 68% or more, 69% or more, 70% or more, 71% or more, 72% or more, 73% or more, 74% or more, 75% or more, 76% or more, 77% or more, or 78% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 80% or less of the mixture (w/w) comprises C.sub.20-C.sub.45 hydrocarbons (e.g., 79% or less, 78% or less, 77% or less, 76% or less, 75% or less, 74% or less, 73% or less, 72% or less, 71% or less, 70% or less, 69% or less, 68% or less, 67% or less, 66% or less, 65% or less, 64% or less, 63% or less, or 62% or less). The amount of the mixture comprising C.sub.20-C.sub.45 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 60% to 80% of the

mixture (w/w) comprises C.sub.20-C.sub.45 hydrocarbons (e.g., from 60% to 70%, from 70% to 80%, from 60% to 65%, from 65% to 70%, from 70% to 75%, from 75% to 80%, from 60% to 75%, from 65% to 80%, or from 65% to 75%).

(126) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 80% or more of the mixture (w/w) can comprise C.sub.9-C.sub.33 hydrocarbons (e.g., 81% or more, 82% or more, 83% or more, 84% or more, 85% or more, 86% or more, 87% or more, or 88% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 90% or less of the mixture (w/w) can comprise C.sub.9-C.sub.33 hydrocarbons (e.g., 89% or less, 88% or less, 87% or less, 86% or less, 85% or less, 84% or less, 83% or less, or 82% or less). The amount of the mixture comprising C.sub.9-C.sub.33 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can comprise a mixture of different hydrocarbons, any of which can optionally be substituted, and from 80% to 90% of the mixture (w/w) can comprise C.sub.9-C.sub.33 hydrocarbons (e.g., from 80% to 85%, from 85% to 90%, from 80% to 82%, from 82% to 84%, from 84% to 86%, from 86% to 88%, from 88% to 90%, from 80% to 88%, from 80% to 86%, from 80% to 84%, from 82% to 90%, from 84% to 90%, from 86% to 90%, from 81% to 89%, or from 82% to 88%).

(127) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 95% or more of the mixture (w/w) comprises C.sub.9-C.sub.46 hydrocarbons (e.g., 95.5% or more, 96% or more, 96.5% or more, 97% or more, 97.5% or more, or 98% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 99% or less of the mixture (w/w) comprises C.sub.9-C.sub.46 hydrocarbons (e.g., 98.5% or less, 98% or less, 97.5% or less, 97% or less, 96.5% or less, or 96% or less). The amount of the mixture comprising C.sub.9-C.sub.46 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 95% to 99% of the mixture (w/w) comprises C.sub.9-C.sub.46 hydrocarbons (e.g., from 95% to 97%, from 97% to 99%, from 95% to 96%, from 96% to 97%, from 97% to 98%, from 98% to 99%, from 95% to 98%, from 96% to 99%, or from 96% to 98%).

(128) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 20% or more of the mixture (w/w) comprises C.sub.9-C.sub.20 hydrocarbons (e.g., 21% or more, 22% or more, 23% or more, 24% or more, 25% or more, 26% or more, 27% or more, or 28% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 30% or less of the mixture (w/w) comprises C.sub.9-C.sub.20 hydrocarbons (e.g., 29% or less, 28% or less, 27% or less, 26% or less, 25% or less, 24% or less, 23% or less, or 22% or less). The amount of the mixture comprising C.sub.9-C.sub.20 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 20% to 30% of the mixture (w/w) comprises C.sub.9-C.sub.20 hydrocarbons (e.g., from 20% to 25%, from 25% to 30%, from 20% to 22%, from 22% to 24%, from 24% to 26%, from 26% to 28%, from 28% to 30%, from 20% to 28%, from 20% to 26%, from 20% to 24%, from 22% to 30%, from 24% to 30%, from 26% to 30%, from 21% to 29%, or from 22% to 28%).

(129) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 20% or more of the mixture (w/w) comprises C.sub.20-C.sub.24 hydrocarbons (e.g., 21% or more, 22% or more, 23% or more, 24% or more, 25% or more, 26% or more, 27% or more, or 28% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 30% or less of the mixture (w/w) comprises C.sub.20-C.sub.24 hydrocarbons (e.g., 29% or less, 28% or less, 27% or less, 26% or less, 25% or less, 24% or less, 23% or less, or 22% or less). The amount of the mixture comprising

C.sub.20-C.sub.24 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 20% to 30% of the mixture (w/w) comprises C.sub.20-C.sub.24 hydrocarbons (e.g., from 20% to 25%, from 25% to 30%, from 20% to 22%, from 22% to 24%, from 24% to 26%, from 26% to 28%, from 28% to 30%, from 20% to 28%, from 20% to 26%, from 20% to 24%, from 22% to 30%, from 24% to 30%, from 26% to 30%, from 21% to 29%, or from 22% to 28%).

(130) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 20% or more of the mixture (w/w) comprises C.sub.24-C.sub.28 hydrocarbons (e.g., 21% or more, 22% or more, 23% or more, 24% or more, 25% or more, 26% or more, 27% or more, or 28% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 30% or less of the mixture (w/w) comprises C.sub.24-C.sub.28 hydrocarbons (e.g., 29% or less, 28% or less, 27% or less, 26% or less, 25% or less, 24% or less, 23% or less, or 22% or less). The amount of the mixture comprising C.sub.24-C.sub.28 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 20% to 30% of the mixture (w/w) comprises C.sub.24-C.sub.28 hydrocarbons (e.g., from 20% to 25%, from 25% to 30%, from 20% to 22%, from 22% to 24%, from 24% to 26%, from 26% to 28%, from 28% to 30%, from 20% to 28%, from 20% to 26%, from 20% to 24%, from 22% to 30%, from 24% to 30%, from 26% to 30%, from 21% to 29%, or from 22% to 28%).

(131) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 10% or more of the mixture (w/w) comprises C.sub.28-C.sub.32 hydrocarbons (e.g., 11% or more, 12% or more, 13% or more, 14% or more, 15% or more, 16% or more, 17% or more, or 18% or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 20% or less of the mixture (w/w) comprises C.sub.28-C.sub.32 hydrocarbons (e.g., 19% or less, 18% or less, 17% or less, 16% or less, 15% or less, 14% or less, 13% or less, or 12% or less). The amount of the mixture comprising C.sub.28-C.sub.32 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 10% to 20% of the mixture (w/w) comprises C.sub.28-C.sub.32 hydrocarbons (e.g., from 10% to 15%, from 15% to 20%, from 10% to 12%, from 12% to 14%, from 14% to 16%, from 16% to 18%, from 18% to 20%, from 10% to 18%, from 10% to 16%, from 10% to 14%, from 12% to 20%, from 14% to 20%, from 16% to 20%, from 11% to 19%, or from 12% to 18%).

(132) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 20-30% (e.g., 25-30%) C.sub.9-C.sub.20 hydrocarbons, 20-30% (e.g., 20-25%) C.sub.20-C.sub.24 hydrocarbons, 20-30% (e.g., 20-25%) C.sub.24-C.sub.28 hydrocarbons, and 10-20% (e.g., 10-15%) C.sub.28-C.sub.32 hydrocarbons. In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 25-30% C.sub.9-C.sub.20 hydrocarbons, 20-25% C.sub.20-C.sub.24 hydrocarbons, 20-25% C.sub.24-C.sub.28 hydrocarbons, and 10-15% C.sub.28-C.sub.32 hydrocarbons.

(133) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture is substantially free of C.sub.1-C.sub.8 hydrocarbons.

(134) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises saturated hydrocarbons (e.g., linear, branched, and/or cyclic alkanes), unsaturated (non-aromatic) hydrocarbons (e.g., linear, branched, and/or cyclic alkenes and/or alkynes), and aromatic hydrocarbons. For example, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture

comprises 80 wt. % or more saturated hydrocarbons (e.g., 81 wt. % or more, 82 wt. % or more, 83 wt. % or more, 84 wt. % or more, 85 wt. % or more, 86 wt. % or more, 87 wt. % or more, 88 wt. % or more, 89 wt. % or more, 90 wt. % or more, 91 wt. % or more, 92 wt. % or more, 93 wt. % or more, 94 wt. % or more, 95 wt. % or more, 96 wt. % or more, 97 wt. % or more, 98 wt. % or more, or 99 wt. % or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 100 wt. % or less saturated hydrocarbons (e.g., 99 wt. % or less, 98 wt. % or less, 97 wt. % or less, 96 wt. % or less, 95 wt. % or less, 94 wt. % or less, 93 wt. % or less, 92 wt. % or less, 91 wt. % or less, 90 wt. % or less, 89 wt. % or less, 88 wt. % or less, 87 wt. % or less, 86 wt. % or less, 85 wt. % or less, 84 wt. % or less, 83 wt. % or less, or 82 wt. % or less). The amount of the mixture comprising saturated hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can comprise a mixture of different hydrocarbons, any of which can optionally be substituted, and from 80 wt. % to 100 wt. % of the mixture can comprise saturated hydrocarbons (e.g., from 80 wt. % to 90 wt. %, from 90 wt. % to 100 wt. %, from 80 wt. % to 85 wt. %, from 85 wt. % to 90 wt. %, from 90 wt. % to 95 wt. %, from 95 wt. % to 100 wt. %, from 80 wt. % to 98 wt. %, from 80 wt. % to 96 wt. %, from 80 wt. % to 94 wt. %, from 80 wt. % to 92 wt. %, from 80 wt. % to 88 wt. %, from 80 wt. % to 86 wt. %, from 80 wt. % to 84 wt. %, from 80 wt. % to 82 wt. %, from 82 wt. % to 100 wt. %, from 84 wt. % to 100 wt. %, from 86 wt. % to 100 wt. %, from 88 wt. % to 100 wt. %, from 92 wt. % to 100 wt. %, from 94 wt. % to 100 wt. %, from 96 wt. % to 100 wt. %, from 98 wt. % to 100 wt. %, from 82 wt. % to 98 wt. %, from 85 wt. % to 99 wt. %, from 85 wt. % to 87 wt. %, or from 97 wt. % to 99 wt. %).

(135) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 0 wt. % or more unsaturated (non-aromatic) hydrocarbons (e.g., 0.1 wt. % or more, 0.2 wt. % or more, 0.3 wt. % or more, 0.4 wt. % or more, 0.5 wt. % or more, 0.6 wt. % or more, 0.7 wt. % or more, 0.8 wt. % or more, 0.9 wt. % or more, 1 wt. % or more, 1.25 wt. % or more, 1.5 wt. % or more, 1.75 wt. % or more, 2 wt. % or more, 2.25 wt. % or more, 2.5 wt. % or more, 3 wt. % or more, 3.5 wt. % or more, or 4 wt. % or more). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 5 wt. % or less unsaturated (non-aromatic) hydrocarbons (e.g., 4.5 wt. % or less, 4 wt. % or less, 3.5 wt. % or less, 3 wt. % or less, 2.5 wt. % or less, 2.25 wt. % or less, 2 wt. % or less, 1.75 wt. % or less, 1.5 wt. % or less, 1.25 wt. % or less, 1 wt. % or less, 0.9 wt. % or less, 0.8 wt. % or less, 0.7 wt. % or less, 0.6 wt. % or less, 0.5 wt. % or less, 0.4 wt. % or less, 0.3 wt. % or less, or 0.2 wt. % or less). The amount of the mixture comprising unsaturated (non-aromatic) hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can comprise a mixture of different hydrocarbons, any of which can optionally be substituted, and from 0 to 5 wt. % of the mixture can comprise unsaturated (non-aromatic) hydrocarbons (e.g., from 0 to 2.5 wt. %, from 2.5 to 5 wt. %, from 0 to 1 wt. %, from 1 to 2 wt. %, from 2 to 3 wt. %, from 3 to 4 wt. %, from 4 to 5 wt. %, from 0 to 4 wt. %, from 0 to 3 wt. %, from 0 to 2 wt. %, from 1 to 5 wt. %, from 2 to 5 wt. %, from 3 to 5 wt. %, from 0.5 to 4.5 wt. %, or from 0.5 to 1.5 wt. %).

(136) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 0 wt. % or more aromatic hydrocarbons (e.g., 0.1 wt. % or more, 0.2 wt. % or more, 0.3 wt. % or more, 0.4 wt. % or more, 0.5 wt. % or more, 0.6 wt. % or more, 0.7 wt. % or more, 0.8 wt. % or more, 0.9 wt. % or more, 1 wt. % or more, 1.25 wt. % or more, 1.5 wt. % or more, 1.75 wt. % or more, 2 wt. % or more, 2.25 wt. % or more, 2.5 wt. % or more, 3 wt. % or more, 3.5 wt. % or more, 4 wt. % or more, 4.5 wt. % or more, 5.5 wt. % or more, 6 wt. % or more, 6.5 wt. % or more, 7 wt. % or more, 7.5 wt. % or more, 8 wt. % or more, 8.5 wt. % or more, 9 wt. % or more, 9.5 wt. % or more, 10 wt. % or more, 10.5 wt. % or more, 11 wt. % or more, 11.5 wt. % or more, 12 wt. % or more, 12.5 wt. % or more, 13 wt. % or more, 13.5 wt. % or more, or 14 wt. % or more). In some examples, the wax comprises a mixture of different

hydrocarbons, any of which can optionally be substituted, and the mixture comprises 15 wt. % or less aromatic hydrocarbons (e.g., 14.5 wt. % or less, 14 wt. % or less, 13.5 wt. % or less, 13 wt. % or less, 12.5 wt. % or less, 12 wt. % or less, 11.5 wt. % or less, 11 wt. % or less, 10.5 wt. % or less, 10 wt. % or less, 9.5 wt. % or less, 9 wt. % or less, 8.5 wt. % or less, 8 wt. % or less, 7.5 wt. % or less, 7 wt. % or less, 6.5 wt. % or less, 6 wt. % or less, 5.5 wt. % or less, 5 wt. % or less, 4.5 wt. % or less, 4 wt. % or less, 3.5 wt. % or less, 3 wt. % or less, 2.5 wt. % or less, 2.25 wt. % or less, 2 wt. % or less, 1.75 wt. % or less, 1.5 wt. % or less, 1.25 wt. % or less, 1 wt. % or less, 0.9 wt. % or less, 0.8 wt. % or less, 0.7 wt. % or less, 0.6 wt. % or less, 0.5 wt. % or less, 0.4 wt. % or less, 0.3 wt. % or less, or 0.2 wt. % or less). The amount of the mixture comprising aromatic hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can comprise a mixture of different hydrocarbons, any of which can optionally be substituted, and from 0 to 15 wt. % of the mixture can comprise aromatic hydrocarbons (e.g., from 0 to 7.5 wt. %, from 7.5 to 15 wt. %, from 0 to 5 wt. %, from 5 to 10 wt. %, from 10 to 15 wt. %, from 0 to 14 wt. %, from 0 to 12 wt. %, from 0 to 10 wt. %, from 0 to 8 wt. %, from 0 to 6 wt. %, from 0 to 4 wt. %, from 0 to 2 wt. %, from 0 to 1 wt. %, from 1 to 15 wt. %, from 2 to 15 wt. %, from 4 to 15 wt. %, from 6 to 15 wt. %, from 8 to 15 wt. %, from 12 to 15 wt. %, from 0.5 to 14.5 wt. %, from 1 to 14 wt. %, or from 12 to 14 wt. %).

(137) In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 80-100 wt. % saturated hydrocarbons (e.g., 85-90 wt. % or 95 to 99 wt. %); 0-5 wt. % unsaturated (non-aromatic) hydrocarbons (e.g., 0-2.5 wt. %, or 0-1.5 wt. %); and 0-15 wt. % aromatic hydrocarbons (e.g., 0-2.5 wt. %, or 12-14 wt. %). In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 85-90 wt. % saturated hydrocarbons; 0-2.5 wt. % unsaturated (non-aromatic) hydrocarbons; and 12-14 wt. % aromatic hydrocarbons. In some examples, the wax comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 95-99 wt. % saturated hydrocarbons; 0-1.5 wt. % unsaturated (non-aromatic) hydrocarbons; and 0-2.5 wt. % aromatic hydrocarbons.

(138) The wax can, for example, have a melting point of 40° C. or more. In some examples, the wax can have a melting point of 55° C. or less. The melting point of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a melting point of from 40° C. to 55° C. (e.g., from 40° C. to 50° C., or from 43° C. to 48° C.). The melting point of the wax can be determined by any suitable method, such as those known in the art. In some examples, the melting point of the wax is determined using ASTM D 127.

(139) The wax can, for example, have a congealing point of 40° C. or more. In some examples, the wax can have a congealing point of 55° C. or less. The congealing point of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a congealing point of from 40° C. to 55° C. (e.g., from 45° C. to 51° C.). The congealing point of the wax can be determined by any suitable method, such as those known in the art. In some examples, the congealing point of the wax is determined using ASTM D 938.

(140) The wax can, for example, have a final boiling point of 950° F. or more. In some examples, the wax can have a final boiling point of 1,300° F. or less. The final boiling point of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a final boiling point of from 950° F. to 1,300° F. (e.g., from 950° F. to 1,250° F., from 1,100° F. to 1,250° F., or from 995° F. to 1,235° F.). The final boiling point of the wax can be determined by any suitable method, such as those known in the art. In some examples, the final boiling point of the wax is determined using ASTM D 7169.

(141) The wax can, for example, have a pour point of 30° F. or more. In some examples, the wax can have a pour point of 60° F. or less. The pour point of the wax can range from any of the

minimum values described above to any of the maximum values described above. For example, the wax can have a pour point of from 30° F. to 60° F. (e.g., from 30° F. to 50° F., from 33° F. to 52° F., or from 45° F. to 60° F.). The pour point of the wax can be determined by any suitable method, such as those known in the art. In some examples, the pour point of the wax is determined using ASTM D 97.

(142) In some examples, the wax can include one or more contaminants. Contaminants can, for example, comprise an alkali metal, an alkaline earth metal, a transition metal, a basic metal, a semimetal, a nonmetal, a halogen, a salt or compound thereof, or a combination thereof. Examples of contaminants include, but are not limited to, lithium, sodium, beryllium, magnesium, calcium, strontium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc, molybdenum, cadmium, mercury, aluminum, titanium silicon, tin, lead, nitrogen, phosphorus, arsenic, antimony, oxygen, sulfur, selenium, fluorine, chlorine, bromine, compounds thereof, and combinations thereof. In some examples, the wax includes a contaminant comprising chloride, nitrogen, silicon, sodium, iron, phosphorus, sulfur, calcium, nickel, copper, vanadium, or a combination thereof.

(143) Contaminants are introduced during plastic formulation and manufacturing processes during the first life of plastic in conjunction with the source and collection method of the plastics.

(144) For example, chlorine sources in used plastics can comprise PVDC layers. PVDC is often used as a layer or coating in food and pharmaceutical packaging applications because it provides excellent barrier properties against moisture, UV light, acids, salts, and detergents as well as having good transparency. Despite design for recyclability formulation changes, PVDC is forecasted to increase at 3.2% annually through 2028 in the US. Packaging converters produce a range of monolayer and multi-layer packaging. Both types can become mixed in recycled streams. Post-consumer sources will contain higher volumes of materials containing chlorine sources that can be difficult to differentiate and remove through standard sorting techniques.

(145) Nitrogen sources in used plastics can, for example, be derived from depolymerization of nylon (e.g., Nylon 6 (PA-6), Nylon-66 (PA-66)) in used plastic sources, often from food and industrial packaging materials. Nylon is used in multi-layer flexible packing films to protect oxygen-sensitive foods or when excellent oil and grease resistance and high mechanical strength are required, such as for processed meats and fish, and cheese and other dairy products. Nylon also provides a wide cold to hot temperature range (e.g., -60° C. to 150° C.), which enables foods to move through freezer to the microwave/oven without packaging degradation. In industrial packaging, nylon is often used as a reinforcing layer to provide high mechanical strength and excellent abrasion and puncture resistance (for example, in polypropylene supersacks that contain a nylon interlayer or straps). Nitrogen can also come from protein (food) residue on plastics that arises from the amino acids in decomposed protein. Post-consumer sources will contain higher volumes of materials containing nitrogen sources that can be difficult to differentiate and remove through standard sorting techniques.

(146) Silicon sources in used plastics can, for example, comprise silica desiccant packages. In food packaging and processing plants, silicon products are widely used as release agents in a wide variety of materials and equipment, leaving residue on plastic surfaces. Silicon is also an additive that can be added to a wide range of materials to change the appearance, extrusion properties, and/or end-product characteristics; this applies to films as well as two-dimensional plastics. Post-consumer sources will contain higher volumes of materials containing silicon sources that can be difficult to differentiate and remove through standard sorting techniques.

(147) Silicon dioxide can be applied in a very thin coating to plastics, specifically polyethylene, polypropylene, and/or polystyrene, to act as a barrier layer to improve the shelf life of oxygen and moisture sensitive food. This thin coating can be applied by a vacuum or plasma deposition process; the barrier layer and the plastic forms a covalent bond. The SiO₂ barrier coatings are chemically inert and enable benefits in rigid and flexible food packaging applications, including,

but not limited to, reducing oxygen and moisture permeability of plastics, ensuring aroma protection and retention of the smell and taste of contents, not sensitive to fluctuations in temperature and humidity, well-suited for pasteurization and sterilization processes, and can increase shelf life of foods without the addition of preservatives. The SiO₂ coatings are thin, e.g. significantly thinner than a human hair, and therefore have a negligible impact on the packing weight. For this reason, coated packaging is considered a mono-material that can be mechanically recycled. Recyclability initiatives are promoting the use of SiO₂ coatings as a replacement for PVDC and Nylon barriers in flexible and rigid packaging. Although these guidelines are intended for mechanically recycled plastics, several packaging forms and formulations are better suited for pyrolysis-based advanced recycling. SiO₂ coatings have the potential to be the “gift that keeps on giving”, especially when used in rigid and flexible polyethylene and polypropylene plastics that are mechanically recycled initially, which, after a few cycles, will then eventually become the used plastic feedstocks for advanced recycling; the silicon is predicted to accumulate and carry forward into each successive application.

(148) Phosphorus-containing flame retardants are widely used in plastics where its rapid oxidation consumes all the oxygen present, thereby stopping the fire. Plastics commonly containing these flame retardants include, but are not limited to, engineered plastics, polyurethane foams, polyamides (e.g., nylon) and glass-fiber reinforced nylon, polyethylene and EVA co-polymers, and intumescent coatings on foams and polypropylene textiles. Phosphate esters are also used as flame retardant plasticizers in PVC, high impact polystyrene (HIPS), polycarbonate (PC), and acrylonitrile butadiene styrene (ABS). Phosphorus sources also include agricultural applications, such as residual glyphosate in HDPE containers and residual phosphorus fertilizers on ground-level films (e.g., mulch films). Post-consumer sources will contain higher volumes of materials containing phosphorus sources that can be difficult to differentiate and remove through standard sorting techniques.

(149) Sources of sulfur, calcium, sodium, iron, phosphorus, or a combination thereof are additives, surface residues, and residual contamination of the incoming post-consumer and/or post-industrial plastics. A wash step can potentially remove certain surface residues, but would add cost and complexity to the advanced (e.g., pyrolysis based) recycling process. Accordingly, post-consumer sources will contain higher volumes of materials containing sources of sulfur, calcium, sodium, iron, phosphorus, or a combination thereof that can be difficult to differentiate and remove through standard sorting techniques.

(150) Copper alloys are commonly and increasingly used to create molds for plastic injection molding processes due to their high thermal conductivity that removes hot spots, reduces warpage and reduces cycle time, ease of machining by a variety of processes, and corrosion resistance to water, cooling fluids and the plastics being injected. Copper alloys often contain nickel and silicon. Plastics manufactured in copper alloy molds can have residual amounts of copper, nickel, and silicon on their surface. In addition, the plating of plastic with nickel and copper can be an effective means of protecting a substrate against corrosion from environmental exposure and make it more resistant to damage from chemicals used in the manufacturing process. In some instances, the plating on plastic can increase the hardness, strength, and wear resistance of the substrate. The presence of copper and nickel on the surface of both pre-consumer and post-consumer sources can be difficult to differentiate and remove through standard sorting techniques.

(151) In some examples, the wax has a total chloride content of 50 ppm or less (e.g., 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax is substantially free of chlorides. The total chloride content of the

wax can be determined by any suitable method, such as those known in the art. For example, the total chloride content of the wax can be determined using ASTM D 7359.

(152) In some examples, the wax has a nitrogen content of 300 ppm or less (e.g., 275 ppm or less, 250 ppm or less, 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax is substantially free of nitrogen. The nitrogen content of the wax can be determined using any suitable method, such as those known in the art. In some examples, the nitrogen content of the wax is determined using ASTM D 4629.

(153) The wax can, for example, have a silicon content of 125 ppm or less (e.g., 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax is substantially free of silicon. The silicon content of the wax can be determined using any suitable method, such as those known in the art. For example, the silicon content of the wax can be determined using ASTM D 5185.

(154) The wax can, for example, have a sodium content of 150 ppm or less (e.g., 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax is substantially free of sodium. The sodium content of the wax can be determined by any suitable method, such as those known in the art. For example, the sodium content of the wax can be determined using ASTM D 5185.

(155) The wax can, for example, have an iron content of 10 ppm or less (e.g., 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax is substantially free of iron. The iron content of the wax can be determined using any suitable method, such as those known in the art. For example, the iron content of the wax can be determined using ASTM D 5185.

(156) The wax can, for example, have a phosphorus content of 50 ppm or less (e.g., 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of phosphorus. The phosphorus content of the wax can be determined using any suitable method, such as those known in the art. In some examples, the phosphorous content of the wax is determined using ASTM D 5185.

(157) The wax can, for example, have a sulfur content of 500 ppm or less (e.g., 475 ppm or less, 450 ppm or less, 425 ppm or less, 400 ppm or less, 375 ppm or less, 350 ppm or less, 325 ppm or less, 300 ppm or less, 275 ppm or less, 250 ppm or less, 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of sulfur. The sulfur content of the wax can be determined by any suitable methods, such as those known in the art. In some examples, the sulfur content of the wax is determined using ASTM D 4294.

(158) The wax can, for example, have a calcium content of 50 ppm or less (e.g., 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of calcium. The calcium content of the wax can be determined using any suitable methods, such as those known in the art. In some examples, the calcium content of the wax can be determined using ASTM D 5185.

(159) The wax can, for example, have a copper content of 10 ppm or less (e.g., 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of copper. The copper content of the wax can be determined using any suitable method, such as those known in the art. For example, the copper content of the wax can be determined using ASTM D 5185.

(160) The wax can, for example, have a nickel content of 100 ppm or less (e.g., 95 ppm or less, 90 ppm or less, 85 ppm or less, 80 ppm or less, 75 ppm or less, 70 ppm or less, 65 ppm or less, 60 ppm or less, 55 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of nickel. The nickel content of the wax can be determined using any suitable method, such as those known in the art. For example, the nickel content can be determined using ASTM D 5185.

(161) The wax can, for example, have a vanadium content of 25 ppm or less (e.g., 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the wax can be substantially free of vanadium. The vanadium content of the wax can be determined using any suitable method, such as those known in the art. For example, the vanadium content of the wax can be determined using ASTM D 5185.

(162) In some examples, the wax has a total chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; and a silicon content of 125 ppm or less. In some examples, the wax has a total

chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 125 ppm or less; and a sodium content of 150 ppm or less. In some examples, the wax has a total chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 125 ppm or less; a sodium content of 150 ppm or less; an iron content of 10 ppm or less; a sulfur content of 500 ppm or less; and a calcium content of 50 ppm or less. In some examples, the wax has a total chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 125 ppm or less; a sodium content of 150 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 500 ppm or less; and a calcium content of 50 ppm or less. In some examples, the wax has a total chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 125 ppm or less; a sodium content of 150 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 500 ppm or less; a calcium content of 50 ppm or less; a copper content of 10 ppm or less; a nickel content of 100 ppm or less; and a vanadium content of 25 ppm or less.

(163) In some examples, the wax has a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; and a silicon content of 100 ppm or less. In some examples, the wax has a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 100 ppm or less; and a sodium content of 10 ppm or less. In some examples, the wax has a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 100 ppm or less; a sodium content of 10 ppm or less; an iron content of 10 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less. In some examples, the wax has a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 100 ppm or less; a sodium content of 10 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less. In some examples, the wax has a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 100 ppm or less; a sodium content of 10 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 10 ppm or less; a calcium content of 5 ppm or less; a copper content of 10 ppm or less; a nickel content of 100 ppm or less; and a vanadium content of 25 ppm or less.

(164) The wax can, for example, have a Gardner color of 2 or more (e.g., 2.5 or more, 3 or more, 3.5 or more, 4 or more, 4.5 or more, 5 or more, 5.5 or more, 6 or more, 6.5 or more, 7 or more, or 7.5 or more). In some examples, the wax can have a Gardner color of 8 or less (e.g., 7.5 or less, 7 or less, 6.5 or less, 6 or less, 5.5 or less, 5 or less, 4.5 or less, 4 or less, 3.5 or less, 3 or less, or 2.5 or less). The Gardner color of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a Gardner color of from 2 to 8 (e.g., from 2 to 5, from 5 to 8, from 2 to 4, from 4 to 6, from 6 to 8, from 2 to 7, from 2 to 6, from 3 to 8, from 4 to 8, from 2.5 to 7.5, from 2.5 to 8, or from 6.5 to 8). The Gardner color of the wax can be determined using any suitable method, such as those known in the art. For example, the Gardner color of the wax can be determined using ASTM D 1500.

(165) The wax can, for example, have an oil content of 5% or more by weight (e.g., 10% or more, 15% or more, 20% or more, 25% or more, 30% or more, 35% or more, or 40% or more). In some examples, the wax can have an oil content of 50% or less (e.g., 45% or less, 40% or less, 35% or less, 30% or less, 25% or less, 20% or less, 15% or less, or 10% or less). The oil content of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have an oil content of from 5% to 50% (e.g., from 5% to 25%, from 25% to 50%, from 5% to 15%, from 10% to 15%, from 15% to 20%, from 20% to 25%, from 25% to 30%, from 30% to 35%, from 35% to 40%, from 40% to 45%, from 45% to 50%, from 5% to 45%, from 5% to 40%, from 5% to 35%, from 5% to 30%, from 5% to 20%, from 5% to 15%, from 10% to 50%, from 15% to 50%, from 20% to 50%, from 30% to 50%, from 35% to 50%, from 40% to 50%, from 10% to 45%, or from 25% to 45%). The oil content of the wax can be determined using any suitable method, for example those known in the art. For

example, the oil content of the wax can be determined using ASTM D 721.

(166) The wax can, for example, have a Reid Vapor Pressure of 12.5 psig or less (e.g., 12 psig or less, 11.5 psig or less, 11 psig or less, 10.5 psig or less, 10 psig or less, 9.5 psig or less, 9 psig or less, 8.5 psig or less, 8 psig or less, 7.5 psig or less, 7 psig or less, 6.5 psig or less, 6 psig or less, 5.5 psig or less, 5 psig or less, 4.5 psig or less, 4 psig or less, 3.5 psig or less, 3 psig or less, or 2.5 psig or less). In some examples, the wax can have a Reid Vapor Pressure of 2 psig or more (e.g., 2.5 psig or more, 3 psig or more, 3.5 psig or more, 4 psig or more, 4.5 psig or more, 5 psig or more, 5.5 psig or more, 6 psig or more, 6.5 psig or more, 7 psig or more, 7.5 psig or more, 8 psig or more, 8.5 psig or more, 9 psig or more, 9.5 psig or more, 10 psig or more, 10.5 psig or more, or 11 psig or more). The Reid Vapor Pressure of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a Reid Vapor Pressure of from 2 to 12.5 psig (e.g., from 5 to 7 psig, from 7 to 12.5 psig, from 2 to 4 psig, from 4 to 6 psig, from 6 to 8 psig, from 8 to 10 psig, from 10 to 12.5 psig, from 2 to 12 psig, from 2 to 11 psig, from 2 to 10 psig, from 2 to 9 psig, from 2 to 8 psig, from 2 to 6 psig, from 2 to 5 psig, from 3 to 12.5 psig, from 4 to 12.5 psig, from 5 to 12.5 psig, from 6 to 12.5 psig, from 7 to 12.5 psig, from 8 to 12.5 psig, from 9 to 12.5 psig, from 3 to 12 psig, from 5 to 11 psig, or from 7 to 10 psig). The Reid Vapor Pressure of the wax can be determined using any suitable method, such as those known in the art. For example, the Reid Vapor Pressure of the wax can be determined using ASTM D 5191.

(167) The wax can, for example, have a water by distillation amount of 0.5 vol. % or less (e.g., 0.45 vol. % or less, 0.4 vol. % or less, 0.35 vol. % or less, 0.3 vol. % or less, 0.25 vol. % or less, 0.2 vol. % or less, 0.15 vol. % or less, 0.1 vol. % or less, 0.075 vol. % or less, 0.05 vol. % or less, 0.025 vol. % or less, or 0.01 vol. % or less). In some examples, the wax can have a water by distillation amount of 0 vol. % or more (e.g., 0.01 vol. % or more, 0.025 vol. % or more, 0.05 vol. % or more, 0.075 vol. % or more, 0.1 vol. % or more, 0.15 vol. % or more, 0.2 vol. % or more, 0.25 vol. % or more, 0.3 vol. % or more, 0.35 vol. % or more, or 0.4 vol. % or more). The amount of water by distillation in the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a water by distillation amount of from 0 to 0.5 vol. % (e.g., from 0 to 0.25 vol. %, from 0.25 to 0.5 vol. %, from 0 to 0.1 vol. %, from 0.1 to 0.2 vol. %, from 0.2 to 0.3 vol. %, from 0.3 to 0.4 vol. %, from 0.4 to 0.5 vol. %, from 0 to 0.4 vol. %, from 0 to 0.3 vol. %, from 0 to 0.2 vol. %, from 0 to 0.05 vol. %, or from 0 to 0.01 vol. %). The amount of water by distillation in the wax can be determined by any suitable method, such as those known in the art. For example, the water by distillation amount in the wax can be determined using ASTM D 95.

(168) The wax can, for example, have a total sediment content of 0.5 vol. % or less (e.g., 0.45 vol. % or less, 0.4 vol. % or less, 0.35 vol. % or less, 0.3 vol. % or less, 0.25 vol. % or less, 0.2 vol. % or less, 0.15 vol. % or less, 0.1 vol. % or less, 0.075 vol. % or less, 0.05 vol. % or less, 0.025 vol. % or less, or 0.01 vol. % or less). In some examples, the wax can have a total sediment content of 0 vol. % or more (e.g., 0.01 vol. % or more, 0.025 vol. % or more, 0.05 vol. % or more, 0.075 vol. % or more, 0.1 vol. % or more, 0.15 vol. % or more, 0.2 vol. % or more, 0.25 vol. % or more, 0.3 vol. % or more, 0.35 vol. % or more, or 0.4 vol. % or more). The total sediment content of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a total sediment content of from 0 to 0.5 vol. % (e.g., from 0 to 0.25 vol. %, from 0.25 to 0.5 vol. %, from 0 to 0.1 vol. %, from 0.1 to 0.2 vol. %, from 0.2 to 0.3 vol. %, from 0.3 to 0.4 vol. %, from 0.4 to 0.5 vol. %, from 0 to 0.4 vol. %, from 0 to 0.3 vol. %, from 0 to 0.2 vol. %, from 0 to 0.05 vol. %, or from 0 to 0.01 vol. %). The total sediment content of the wax can be determined by any suitable method, such as those known in the art. For example, the total sediment content of the wax can be determined using ASTM D 4870.

(169) The wax can, for example, have an n-heptane insoluble content of 0.5 wt. % or less (e.g., 0.45 wt. % or less, 0.4 wt. % or less, 0.35 wt. % or less, 0.3 wt. % or less, 0.25 wt. % or less, 0.2

wt. % or less, 0.15 wt. % or less, 0.1 wt. % or less, 0.075 wt. % or less, 0.05 wt. % or less, 0.025 wt. % or less, or 0.01 wt. % or less). In some examples, the wax can have an n-heptane insoluble content of 0 wt. % or more (e.g., 0.01 wt. % or more, 0.025 wt. % or more, 0.05 wt. % or more, 0.075 wt. % or more, 0.1 wt. % or more, 0.15 wt. % or more, 0.2 wt. % or more, 0.25 wt. % or more, 0.3 wt. % or more, 0.35 wt. % or more, or 0.4 wt. % or more). The n-heptane insoluble content of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have an n-heptane insoluble content of from 0 to 0.5 wt. % (e.g., from 0 to 0.25 wt. %, from 0.25 to 0.5 wt. %, from 0 to 0.1 wt. %, from 0.1 to 0.2 wt. %, from 0.2 to 0.3 wt. %, from 0.3 to 0.4 wt. %, from 0.4 to 0.5 wt. %, from 0 to 0.4 wt. %, from 0 to 0.3 wt. %, from 0 to 0.2 wt. %, from 0 to 0.05 wt. %, or from 0 to 0.01 wt. %). The n-heptane insoluble content of the wax can be determined by any suitable method, such as those known in the art. For example, the n-heptane insoluble content of the wax can be determined using ASTM D 3279.

(170) The wax can, for example, have a total acid number of 1 mg KOH/g or less (e.g., 0.9 mg KOH/g or less, 0.8 mg KOH/g or less, 0.7 mg KOH/g or less, 0.6 mg KOH/g or less, 0.5 mg KOH/g or less, 0.4 mg KOH/g or less, 0.3 mg KOH/g or less, 0.2 mg KOH/g or less, or 0.1 mg KOH/g or less). In some examples, the wax can have a total acid number of 0 mg KOH/g or more (e.g., 0.1 mg KOH/g or more, 0.2 mg KOH/g or more, 0.3 mg KOH/g or more, 0.4 mg KOH/g or more, 0.5 mg KOH/g or more, 0.6 mg KOH/g or more, 0.7 mg KOH/g or more, 0.8 mg KOH/g or more, or 0.9 mg KOH/g or more). The total acid number of the wax can range from any of the minimum values described above to any of the maximum values described above. For example, the wax can have a total acid number of from 0 to 1 mg KOH/g (e.g., from 0 to 0.5 mg KOH/g, from 0.5 to 1 mg KOH/g, from 0 to 0.2 mg KOH/g, from 0.2 to 0.4 mg KOH/g, from 0.4 to 0.6 mg KOH/g, from 0.6 to 0.8 mg KOH/g, from 0.8 to 1 mg KOH/g, from 0 to 0.8 mg KOH/g, from 0 to 0.6 mg KOH/g, from 0 to 0.4 mg KOH/g, or from 0 to 0.1 mg KOH/g). The total acid number of the wax can be determined using any suitable method, such as those known in the art. For example, the total acid number of the wax can be determined using ASTM D 664.

(171) In some examples, the wax has a Reid Vapor Pressure of 12.5 psig or less; and a final boiling point of 950° F. to 1,300° F. In some examples, the wax has a Reid Vapor Pressure of from 7 to 10 psig; and a final boiling point of from 995° F. to 1,235° F.

(172) In some examples, the wax has a Reid Vapor Pressure of 12.5 psig or less; and a pour point of 30° F. to 60° F. In some examples, the wax has a Reid Vapor Pressure of from 7 to 10 psig; and a pour point of from 33° F. to 52° F.

(173) In some examples, the wax has a final boiling point of 950° F. to 1,300° F.; and a pour point of 30° F. to 60° F. In some examples, the wax has a final boiling point of from 995° F. to 1,235° F.; and a pour point of from 33° F. to 52° F.

(174) In some examples, the wax has a Reid Vapor Pressure of 12.5 psig or less; a final boiling point of 950° F. to 1,300° F.; and a pour point of 30° F. to 60° F. In some examples, the wax has a Reid Vapor Pressure of from 7 to 10 psig; a final boiling point of from 995° F. to 1,235° F.; and a pour point of from 33° F. to 52° F.

(175) In some examples, the wax has a Reid Vapor Pressure of 12.5 psig or less; a final boiling point of 950° F. to 1,300° F.; a pour point of 30° F. to 60° F.; a total chloride content of 50 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 125 ppm or less; a sodium content of 150 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 500 ppm or less; and a calcium content of 50 ppm or less. In some examples, the wax has a Reid Vapor Pressure of from 7 to 10 psig; a final boiling point of from 995° F. to 1,235° F.; a pour point of from 33° F. to 52° F.; a total chloride content of 25 ppm or less; a nitrogen content of 300 ppm or less; a silicon content of 100 ppm or less; a sodium content of 10 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 50 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less.

(176) In some examples, the wax is a raw pyrolysis product, meaning the wax is produced by a method that substantially excludes any hydrotreatment or further refining steps after pyrolysis.

(177) Oil

(178) Also disclosed herein are oils derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics. In some examples, the oil can be produced via pyrolysis at an industrial scale.

(179) The oil can, for example, have a number average molecular weight and/or a weight average molecular weight of 50 Daltons or more (e.g., 55 Daltons or more, 60 Daltons or more, 65 Daltons or more, 70 Daltons or more, 75 Daltons or more, 80 Daltons or more, 85 Daltons or more, 90 Daltons or more, 95 Daltons or more, 100 Daltons or more, 110 Daltons or more, 120 Daltons or more, 130 Daltons or more, 140 Daltons or more, 150 Daltons or more, 160 Daltons or more, 170 Daltons or more, 180 Daltons or more, 190 Daltons or more, 200 Daltons or more, 225 Daltons or more, 250 Daltons or more, 275 Daltons or more, 300 Daltons or more, or 325 Daltons or more). In some examples, the oil can have a number average molecular weight and/or a weight average molecular weight of 350 Daltons or less (e.g., 325 Daltons or less, 300 Daltons or less, 275 Daltons or less, 250 Daltons or less, 225 Daltons or less, 200 Daltons or less, 190 Daltons or less, 180 Daltons or less, 170 Daltons or less, 160 Daltons or less, 150 Daltons or less, 140 Daltons or less, 130 Daltons or less, 120 Daltons or less, 110 Daltons or less, 100 Daltons or less, 95 Daltons or less, 90 Daltons or less, 85 Daltons or less, 80 Daltons or less, 75 Daltons or less, 70 Daltons or less, 65 Daltons or less, or 60 Daltons or less). The number average molecular weight and/or a weight average molecular weight of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a number average molecular weight and/or a weight average molecular weight of from 50 to 350 Daltons (e.g., from 50 to 200 Daltons, from 200 to 350 Daltons, from 50 to 150 Daltons, from 150 to 250 Daltons, from 250 to 350 Daltons, from 50 to 300 Daltons, from 50 to 250 Daltons, from 50 to 100 Daltons, from 75 to 350 Daltons, from 100 to 350 Daltons, from 150 to 350 Daltons, from 300 to 350 Daltons, from 75 to 325 Daltons, or from 100 to 300 Daltons).

(180) The oil comprises a mixture of different hydrocarbons (e.g., linear, branched, cyclic, acyclic, saturated, unsaturated, aromatic, non-aromatic, etc.), any of which can optionally be substituted. In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 90% or more of the mixture (w/w) comprises C.sub.1-C.sub.20 hydrocarbons (e.g., 90.5% or more, 91% or more, 91.5% or more, 92% or more, 92.5% or more, 93% or more, 93.5% or more, 94% or more, 94.5% or more, 95% or more, 95.5% or more, 96% or more, 96.5% or more, 97% or more, 97.5% or more, 98% or more, 98.5% or more, or 99% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 100% or less of the mixture (w/w) comprises C.sub.1-C.sub.20 hydrocarbons (e.g., 99.5% or less, 99% or less, 98.5% or less, 98% or less, 97.5% or less, 97% or less, 96.5% or less, 96% or less, 95.5% or less, 95% or less, 94.5% or less, 94% or less, 93.5% or less, 93% or less, 92.5% or less, 92% or less, 91.5% or less, or 91% or less). The amount of the mixture comprising C.sub.1-C.sub.20 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 90% to 100% of the mixture (w/w) can comprise C.sub.1-C.sub.20 hydrocarbons (e.g., from 90% to 95%, from 95% to 100%, from 90% to 92%, from 92% to 94%, from 94% to 96%, from 96% to 98%, from 98% to 100%, from 90% to 98%, from 90% to 96%, from 90% to 94%, from 92% to 100%, from 94% to 100%, from 96% to 100%, from 91% to 99%, from 92% to 98%, or from 92% to 96%).

(181) The oil comprises a mixture of different hydrocarbons (e.g., linear, branched, cyclic, acyclic, saturated, unsaturated, aromatic, non-aromatic, etc.), any of which can optionally be substituted. In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 90% or more of the mixture (w/w) comprises C.sub.4-C.sub.20 hydrocarbons

(e.g., 90.5% or more, 91% or more, 91.5% or more, 92% or more, 92.5% or more, 93% or more, 93.5% or more, 94% or more, 94.5% or more, 95% or more, 95.5% or more, 96% or more, 96.5% or more, 97% or more, 97.5% or more, 98% or more, 98.5% or more, or 99% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 100% or less of the mixture (w/w) comprises C.sub.4-C.sub.20 hydrocarbons (e.g., 99.5% or less, 99% or less, 98.5% or less, 98% or less, 97.5% or less, 97% or less, 96.5% or less, 96% or less, 95.5% or less, 95% or less, 94.5% or less, 94% or less, 93.5% or less, 93% or less, 92.5% or less, 92% or less, 91.5% or less, or 91% or less). The amount of the mixture comprising C.sub.4-C.sub.20 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 90% to 100% of the mixture (w/w) can comprise C.sub.4-C.sub.20 hydrocarbons (e.g., from 90% to 95%, from 95% to 100%, from 90% to 92%, from 92% to 94%, from 94% to 96%, from 96% to 98%, from 98% to 100%, from 90% to 98%, from 90% to 96%, from 90% to 94%, from 92% to 100%, from 94% to 100%, from 96% to 100%, from 91% to 99%, from 92% to 98%, or from 92% to 96%).

(182) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 0% or more of the mixture (w/w) can comprise C.sub.12-C.sub.29 hydrocarbons (e.g., 0.5% or more, 1% or more, 1.5% or more, 2% or more, 2.5% or more, 3% or more, 3.5% or more, 4% or more, 4.5% or more, 5% or more, 5.5% or more, 6% or more, 6.5% or more, 7% or more, 7.5% or more, 8% or more, 8.5% or more, or 9% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 10% or less of the mixture (w/w) can comprise C.sub.12-C.sub.29 hydrocarbons (e.g., 9.5% or less, 9% or less, 8.5% or less, 8% or less, 7.5% or less, 7% or less, 6.5% or less, 6% or less, 5.5% or less, 5% or less, 4.5% or less, 4% or less, 3.5% or less, 3% or less, 2.5% or less, 2% or less, 1.5% or less, or 1% or less). The amount of the mixture comprising C.sub.12-C.sub.29 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 0% to 10% of the mixture (w/w) can comprise C.sub.12-C.sub.29 hydrocarbons (e.g., from 0% to 5%, from 5% to 10%, from 0% to 2%, from 2% to 4%, from 4% to 6%, from 6% to 8%, from 8% to 10%, from 0% to 8%, from 0% to 6%, from 0% to 4%, from 1% to 10%, from 2% to 10%, from 4% to 10%, from 6% to 10%, from 0.5% to 9.5%, from 1% to 9%, or from 2% to 8%).

(183) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 25% or more of the mixture (w/w) comprises C.sub.1-C.sub.8 hydrocarbons (e.g., 25.5% or more, 26% or more, 26.5% or more, 27% or more, 27.5% or more, 28% or more, 28.5% or more, 29% or more, 29.5% or more, 30% or more, 30.5% or more, 31% or more, 31.5% or more, 32% or more, 32.5% or more, 33% or more, 33.5% or more, or 34% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 35% or less of the mixture (w/w) comprises C.sub.1-C.sub.8 hydrocarbons (e.g., 34.5% or less, 34% or less, 33.5% or less, 33% or less, 32.5% or less, 32% or less, 31.5% or less, 31% or less, 30.5% or less, 30% or less, 29.5% or less, 29% or less, 28.5% or less, 28% or less, 27.5% or less, 27% or less, 26.5% or less, or 26% or less). The amount of the mixture comprising C.sub.1-C.sub.8 hydrocarbon can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 25% to 35% of the mixture (w/w) can comprise C.sub.1-C.sub.8 hydrocarbons (e.g., from 25% to 30%, from 30% to 35%, from 25% to 27%, from 27% to 29%, from 29% to 31%, from 31% to 33%, from 33% to 35%, from 25% to 33%, from 25% to 31%, from 25% to 29%, from 27% to 35%, from 29% to 35%, from 31% to 35%, from 25.5% to 34.5%, or from 26% to 34%).

(184) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can

optionally be substituted, and 25% or more of the mixture (w/w) comprises C.sub.4-C.sub.8 hydrocarbons (e.g., 25.5% or more, 26% or more, 26.5% or more, 27% or more, 27.5% or more, 28% or more, 28.5% or more, 29% or more, 29.5% or more, 30% or more, 30.5% or more, 31% or more, 31.5% or more, 32% or more, 32.5% or more, 33% or more, 33.5% or more, or 34% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 35% or less of the mixture (w/w) comprises C.sub.4-C.sub.8 hydrocarbons (e.g., 34.5% or less, 34% or less, 33.5% or less, 33% or less, 32.5% or less, 32% or less, 31.5% or less, 31% or less, 30.5% or less, 30% or less, 29.5% or less, 29% or less, 28.5% or less, 28% or less, 27.5% or less, 27% or less, 26.5% or less, or 26% or less). The amount of the mixture comprising C.sub.4-C.sub.8 hydrocarbon can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 25% to 35% of the mixture (w/w) can comprise C.sub.4-C.sub.8 hydrocarbons (e.g., from 25% to 30%, from 30% to 35%, from 25% to 27%, from 27% to 29%, from 29% to 31%, from 31% to 33%, from 33% to 35%, from 25% to 33%, from 25% to 31%, from 25% to 29%, from 27% to 35%, from 29% to 35%, from 31% to 35%, from 25.5% to 34.5%, or from 26% to 34%).

(185) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 55% or more of the mixture (w/w) can comprise C.sub.9-C.sub.20 hydrocarbons (e.g., 55.5% or more, 56% or more, 56.5% or more, 57% or more, 57.5% or more, 58% or more, 58.5% or more, 59% or more, 59.5% or more, 60% or more, 60.5% or more, 61% or more, 61.5% or more, 62% or more, 62.5% or more, 63% or more, 63.5% or more, or 64% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 65% or less of the mixture (w/w) can comprise C.sub.9-C.sub.20 hydrocarbons (e.g., 64.5% or less, 64% or less, 63.5% or less, 63% or less, 62.5% or less, 62% or less, 61.5% or less, 61% or less, 60.5% or less, 60% or less, 59.5% or less, 59% or less, 58.5% or less, 58% or less, 57.5% or less, 57% or less, 56.5% or less, or 56% or less). The amount of the mixture comprising C.sub.9-C.sub.20 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 55% to 65% of the mixture (w/w) can comprise C.sub.9-C.sub.20 hydrocarbons (e.g., from 55% to 60%, from 60% to 65%, from 55% to 57%, from 57% to 59%, from 59% to 61%, from 61% to 63%, from 63% to 65%, from 55% to 63%, from 55% to 61%, from 55% to 59%, from 57% to 65%, from 59% to 65%, from 61% to 65%, from 55.5% to 64.5%, or from 56% to 64%).

(186) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 1% or more of the mixture (w/w) can comprise C.sub.21-C.sub.29 hydrocarbons (e.g., 1.5% or more, 2% or more, 2.5% or more, 3% or more, 3.5% or more, 4% or more, 4.5% or more, 5% or more, 5.5% or more, 6% or more, 6.5% or more, 7% or more, 7.5% or more, 8% or more, 8.5% or more, or 9% or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and 10% or less of the mixture (w/w) can comprise C.sub.21-C.sub.29 hydrocarbons (e.g., 9.5% or less, 9% or less, 8.5% or less, 8% or less, 7.5% or less, 7% or less, 6.5% or less, 6% or less, 5.5% or less, 5% or less, 4.5% or less, 4% or less, 3.5% or less, 3% or less, 2.5% or less, or 2% or less). The amount of the mixture comprising C.sub.21-C.sub.29 hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and from 1% to 10% of the mixture (w/w) can comprise C.sub.21-C.sub.29 hydrocarbons (e.g., from 1% to 4.5%, from 4.5% to 10%, from 1% to 4%, from 4% to 7%, from 7% to 10%, from 1% to 9%, from 1% to 8%, from 1% to 7%, from 1% to 6%, from 1% to 5%, from 1% to 3%, from 2% to 10%, from 3% to 10%, from 4% to 10%, from 5% to 10%, from 6% to 10%, from 8% to 10%, from 1.5% to 9.5%, from 2% to 9%, or from 3% to 8%).

(187) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 25-35% (e.g., 30-35%) C.sub.1-C.sub.8 hydrocarbons, 55-65% (e.g., 60-65%) C.sub.9-C.sub.20 hydrocarbons, and 1-10% (e.g., 3-8%) C.sub.21-C.sub.29 hydrocarbons. In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 30-35% C.sub.1-C.sub.8 hydrocarbons, 60-65% C.sub.9-C.sub.20 hydrocarbons, and 3-8% C.sub.21-C.sub.29 hydrocarbons.

(188) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 25-35% (e.g., 30-35%) C.sub.4-C.sub.8 hydrocarbons, 55-65% (e.g., 60-65%) C.sub.9-C.sub.20 hydrocarbons, and 1-10% (e.g., 3-8%) C.sub.21-C.sub.29 hydrocarbons. In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 30-35% C.sub.4-C.sub.8 hydrocarbons, 60-65% C.sub.9-C.sub.20 hydrocarbons, and 3-8% C.sub.21-C.sub.29 hydrocarbons.

(189) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture is substantially free of hydrocarbons comprising 30 or more carbons.

(190) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises saturated hydrocarbons (e.g., linear, branched, and/or cyclic alkanes), unsaturated (non-aromatic) hydrocarbons (e.g., linear, branched, and/or cyclic alkenes and/or alkynes), and aromatic hydrocarbons. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 90 wt. % or more unsaturated hydrocarbons (e.g., 90.5 wt. % or more, 91 wt. % or more, 91.5 wt. % or more, 92 wt. % or more, 92.5 wt. % or more, 93 wt. % or more, 93.5 wt. % or more, 94 wt. % or more, 94.5 wt. % or more, 95 wt. % or more, 95.5 wt. % or more, 96 wt. % or more, 96.5 wt. % or more, 97 wt. % or more, 97.5 wt. % or more, 98 wt. % or more, 98.5 wt. % or more, or 99 wt. % or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 100 wt. % or less unsaturated hydrocarbons (e.g., 99.5 wt. % or less, 99 wt. % or less, 98.5 wt. % or less, 98 wt. % or less, 97.5 wt. % or less, 97 wt. % or less, 96.5 wt. % or less, 96 wt. % or less, 95.5 wt. % or less, 95 wt. % or less, 94.5 wt. % or less, 94 wt. % or less, 93.5 wt. % or less, 93 wt. % or less, 92.5 wt. % or less, 92 wt. % or less, 91.5 wt. % or less, or 91 wt. % or less). The amount of the mixture comprising unsaturated hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises from 90 wt. % to 100 wt. % unsaturated hydrocarbons (e.g., from 90 to 95 wt. %, from 95 to 100 wt. %, from 90 to 92 wt. %, from 92 to 94 wt. %, from 94 to 96 wt. %, from 96 to 98 wt. %, from 98 to 100 wt. %, from 90 to 98 wt. %, from 90 to 96 wt. %, from 90 to 94 wt. %, from 92 to 100 wt. %, from 94 to 100 wt. %, from 96 to 100 wt. %, from 91 to 99 wt. %, from 92 to 98 wt. %, or from 94 to 96 wt. %).

(191) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 0 wt. % or more unsaturated (non-aromatic) hydrocarbons (e.g., 0.25 wt. % or more, 0.5 wt. % or more, 0.75 wt. % or more, 1 wt. % or more, 1.25 wt. % or more, 1.5 wt. % or more, 1.75 wt. % or more, 2 wt. % or more, 2.25 wt. % or more, 2.5 wt. % or more, 3 wt. % or more, 3.5 wt. % or more, or 4 wt. % or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 5 wt. % or less unsaturated (non-aromatic) hydrocarbons (e.g., 4.5 wt. % or less, 4 wt. % or less, 3.5 wt. % or less, 3 wt. % or less, 2.5 wt. % or less, 2.25 wt. % or less, 2 wt. % or less, 1.75 wt. % or less, 1.5 wt. % or less, 1.25 wt. % or less, 1 wt. % or less, 0.75 wt. % or less, or 0.5 wt. % or less). The amount of unsaturated (non-aromatic) hydrocarbons in the mixture can

range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture can comprise from 0 wt. % to 5 wt. % unsaturated (non-aromatic) hydrocarbons (e.g., from 0 to 2.5 wt. %, from 2.5 to 5 wt. %, from 0 to 1 wt. %, from 1 to 2 wt. %, from 2 to 3 wt. %, from 3 to 4 wt. %, from 4 to 5 wt. %, from 0 to 4 wt. %, from 0 to 3 wt. %, from 0 to 2 wt. %, from 1 to 5 wt. %, from 2 to 5 wt. %, from 3 to 5 wt. %, from 0.5 to 4.5 wt. %, or from 3.5 to 4.5 wt. %).

(192) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 0 wt. % or more aromatic hydrocarbons (e.g., 0.25 wt. % or more, 0.5 wt. % or more, 0.75 wt. % or more, 1 wt. % or more, 1.25 wt. % or more, 1.5 wt. % or more, 1.75 wt. % or more, or 2 wt. % or more). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises 2.5 wt. % or less aromatic hydrocarbons (e.g., 2.25 wt. % or less, 2 wt. % or less, 1.75 wt. % or less, 1.5 wt. % or less, 1.25 wt. % or less, 1 wt. % or less, 0.75 wt. % or less, or 0.5 wt. % or less). The amount of the mixture comprising aromatic hydrocarbons can range from any of the minimum values described above to any of the maximum values described above. For example, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture can comprise from 0 wt. % to 2.5 wt. % aromatic hydrocarbons (e.g., from 0 to 1.25 wt. %, from 1.25 to 2.5 wt. %, from 0 to 0.5 wt. %, from 0.5 to 1 wt. %, from 1 to 1.5 wt. %, from 1.5 to 2 wt. %, from 2 to 2.5 wt. %, from 0 to 2 wt. %, from 0 to 1.5 wt. %, from 0 to 1 wt. %, from 0.5 to 2.5 wt. %, from 1 to 2.5 wt. %, from 1.5 to 2.5 wt. %, from 0.5 to 2 wt. %, or from 1 to 2 wt. %).

(193) In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 90-100 wt. % saturated hydrocarbons (e.g., 94-96 wt. %); 0-5 wt. % unsaturated (non-aromatic) hydrocarbons (e.g., 3.5-4.5 wt. %); and 0-2.5 wt. % aromatic hydrocarbons (e.g., 1-2 wt. %). In some examples, the oil comprises a mixture of different hydrocarbons, any of which can optionally be substituted, and the mixture comprises: 94-96 wt. % saturated hydrocarbons; 3.5-4.5 wt. % unsaturated (non-aromatic) hydrocarbons; and 1-2 wt. % aromatic hydrocarbons.

(194) The oil can, for example, have a final boiling point of 750° F. or more. In some examples, the oil can have a final boiling point of 1,000° F. or less. The final boiling point of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a final boiling point of from 750° F. to 1,000° F. (e.g., from 900° F. to 950° F., from 920° F. to 950° F., or from 935° F. to 950° F.). The final boiling point of the oil can be determined using any suitable method, such as those known in the art. For example, the final boiling point of the oil can be determined using ASTM D 7169.

(195) The oil can, for example, have a pour point of 0° F. or more. In some examples, the oil can have a pour point of 20° F. or less. The pour point of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a pour point of from 0° F. to 20° F. (e.g., from 5° F. to 15° F., from 8° F. to 15° F., or from 10° F. to 15° F.). The pour point of the oil can be determined using any suitable method, such as those known in the art. For example, the pour point of the oil can be determined using ASTM D 97.

(196) In some examples, the oil can include one or more contaminants. Contaminants can for example, comprise an alkali metal, an alkaline earth metal, a transition metal, a basic metal, a semimetal, a nonmetal, a halogen, a salt or compound thereof, or a combination thereof. Examples of contaminants include, but are not limited to, lithium, sodium, beryllium, magnesium, calcium, strontium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc, molybdenum, cadmium, mercury, aluminum, titanium silicon, tin, lead, nitrogen, phosphorus, arsenic, antimony, oxygen, sulfur, selenium, fluorine, chlorine, bromine, compounds thereof, and combinations thereof. In some examples, the oil includes a contaminant comprising chloride,

nitrogen, silicon, sodium, iron, phosphorus, sulfur, calcium, nickel, copper, vanadium, or a combination thereof.

(197) Contaminants are introduced during plastic formulation and manufacturing processes during the first life of plastic in conjunction with the source and collection method of the plastics.

(198) For example, chlorine sources in used plastics can comprise PVDC layers. PVDC is often used as a layer or coating in food and pharmaceutical packaging applications because it provides excellent barrier properties against moisture, UV light, acids, salts, and detergents as well as having good transparency. Despite design for recyclability formulation changes, PVDC is forecasted to increase at 3.2% annually through 2028 in the US. Packaging converters produce a range of monolayer and multi-layer packaging. Both types can become mixed in recycled streams. Post-consumer sources will contain higher volumes of materials containing chlorine sources that can be difficult to differentiate and remove through standard sorting techniques.

(199) Nitrogen sources in used plastics can, for example, be derived from depolymerization of nylon (e.g., Nylon 6 (PA-6), Nylon-66 (PA-66)) in used plastic sources, often from food and industrial packaging materials. Nylon is used in multi-layer flexible packing films to protect oxygen-sensitive foods or when excellent oil and grease resistance and high mechanical strength are required, such as for processed meats and fish, and cheese and other dairy products. Nylon also provides a wide cold to hot temperature range (e.g., -60°C . to 150°C .), which enables foods to move through freezer to the microwave/oven without packaging degradation. In industrial packaging, nylon is often used as a reinforcing layer to provide high mechanical strength and excellent abrasion and puncture resistance (for example, in polypropylene supersacks that contain a nylon interlayer or straps). Nitrogen can also come from protein (food) residue on plastics that arises from the amino acids in decomposed protein. Post-consumer sources will contain higher volumes of materials containing nitrogen sources that can be difficult to differentiate and remove through standard sorting techniques.

(200) Silicon sources in used plastics can, for example, comprise silica desiccant packages. In food packaging and processing plants, silicon products are widely used as release agents in a wide variety of materials and equipment, leaving residue on plastic surfaces. Silicon is also an additive that can be added to a wide range of materials to change the appearance, extrusion properties, and/or end-product characteristics; this applied to films as well as two-dimensional plastics. Post-consumer sources will contain higher volumes of materials containing silicon sources that can be difficult to differentiate and remove through standard sorting techniques.

(201) Silicon dioxide can be applied in a very thin coating to plastics, specifically polyethylene, polypropylene, and/or polystyrene, to act as a barrier layer to improve the shelf life of oxygen and moisture sensitive food. This thin coating can be applied by a vacuum or plasma deposition process; the barrier layer and the plastic form a covalent bond. The SiO_2 barrier coatings are chemically inert and enable benefits in rigid and flexible food packaging applications, including, but not limited to, reducing oxygen and moisture permeability of plastics, ensuring aroma protection and retention of the smell and taste of contents, not sensitive to fluctuations in temperature and humidity, well-suited for pasteurization and sterilization processes, and can increase shelf life of foods without the addition of preservatives. The SiO_2 coatings are thin, e.g. significantly thinner than a human hair, and therefore have a negligible impact on the packing weight. For this reason, coated packaging is considered a mono-material that can be mechanically recycled. Recyclability initiatives are promoting the use of SiO_2 coatings as a replacement for PVDC and Nylon barriers in flexible and rigid packaging. Although these guidelines are intended for mechanically recycled plastics, several packaging forms and formulations are better suited for pyrolysis-based advanced recycling. SiO_2 coatings have the potential to be the “gift that keeps on giving”, especially when used in rigid and flexible polyethylene and polypropylene plastics that are mechanically recycled initially, which, after a few cycles, will then eventually become the used plastic feedstocks for advanced recycling; the silicon is predicted to accumulate and carry forward

into each successive application.

(202) Phosphorus-containing flame retardants are widely used in plastics where its rapid oxidation consumes all the oxygen present, thereby stopping the fire. Plastics commonly containing these flame retardants include, but are not limited to, engineered plastics, polyurethane foams, polyamides (e.g., nylon) and glass-fiber reinforced nylon, polyethylene and EVA co-polymers, and intumescent coatings on foams and polypropylene textiles. Phosphate esters are also used as flame retardant plasticizers in PVC, high impact polystyrene (HIPS), polycarbonate (PC), and acrylonitrile butadiene styrene (ABS). Phosphorus sources also include agricultural applications, such as residual glyphosate in HDPE containers and residual phosphorus fertilizers on ground-level films (e.g., mulch films). Post-consumer sources will contain higher volumes of materials containing phosphorus sources that can be difficult to differentiate and remove through standard sorting techniques.

(203) Sources of sulfur, calcium, sodium, iron, phosphorus, or a combination thereof are additives, surface residues, and residual contamination of the incoming post-consumer and/or post-industrial plastics. A wash step can potentially remove certain surface residues, but would add cost and complexity to the advanced (e.g., pyrolysis based) recycling process. Accordingly, post-consumer sources will contain higher volumes of materials containing sources of sulfur, calcium, sodium, iron, phosphorus, or a combination thereof that can be difficult to differentiate and remove through standard sorting techniques.

(204) Copper alloys are commonly and increasingly used to create molds for plastic injection molding processes due to their high thermal conductivity that removes hot spots, reduces warpage and reduces cycle time, ease of machining by a variety of processes, and corrosion resistance to water, cooling fluids and the plastics being injected. Copper alloys often contain nickel and silicon. Plastics manufactured in copper alloy molds can have residual amounts of copper, nickel, and silicon on their surface. In addition, the plating of plastic with nickel and copper can be an effective means of protecting a substrate against corrosion from environmental exposure and make it more resistant to damage from chemicals used in the manufacturing process. In some instances, the plating on plastic can increase the hardness, strength, and wear resistance of the substrate. The presence of copper and nickel on the surface of both pre-consumer and post-consumer sources can be difficult to differentiate and remove through standard sorting techniques.

(205) In some examples, the oil has a total chloride content of 500 ppm or less (e.g., 475 ppm or less, 450 ppm or less, 425 ppm or less, 400 ppm or less, 375 ppm or less, 350 ppm or less, 325 ppm or less, 300 ppm or less, 275 ppm or less, 250 ppm or less, 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil is substantially free of chlorides. The total chloride content of the oil can be determined using any suitable method. For example, the total chloride content of the oil can be determined using ASTM D 7359.

(206) The oil can, for example, have a nitrogen content of 600 ppm or less (e.g., 575 ppm or less, 550 ppm or less, 525 ppm or less, 500 ppm or less, 475 ppm or less, 450 ppm or less, 425 ppm or less, 400 ppm or less, 375 ppm or less, 350 ppm or less, 325 ppm or less, 300 ppm or less, 275 ppm or less, 250 ppm or less, 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75

ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of nitrogen. The nitrogen content of the oil can be determined using any suitable method, such as those known in the art. For example, the nitrogen content of the oil can be determined using ASTM D 4629.

(207) The oil can, for example, have a silicon content of 2,000 ppm or less (e.g., 1,900 ppm or less, 1,800 ppm or less, 1,700 ppm or less, 1,600 ppm or less, 1,500 ppm or less, 1,400 ppm or less, 1,300 ppm or less, 1,200 ppm or less, 1,100 ppm or less, 1,000 ppm or less, 950 ppm or less, 900 ppm or less, 850 ppm or less, 800 ppm or less, 750 ppm or less, 700 ppm or less, 650 ppm or less, 600 ppm or less, 550 ppm or less, 500 ppm or less, 475 ppm or less, 450 ppm or less, 425 ppm or less, 400 ppm or less, 375 ppm or less, 350 ppm or less, 325 ppm or less, 300 ppm or less, 275 ppm or less, 250 ppm or less, 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of silicon. The silicon content of the oil can be determined using any suitable method, such as those known in the art. For example, the silicon content of the oil can be determined using ASTM D 5185.

(208) The oil can, for example, have a sodium content of 100 ppm or less (e.g., 95 ppm or less, 90 ppm or less, 85 ppm or less, 80 ppm or less, 75 ppm or less, 70 ppm or less, 65 ppm or less, 60 ppm or less, 55 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of sodium. The sodium content of the oil can be determined using any suitable method, such as those known in the art. For example, the sodium content of the oil can be determined using ASTM D 5185.

(209) The oil can, for example, have an iron content of 10 ppm or less (e.g., 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of iron. The iron content of the oil can be determined using any suitable method, such as those known in the art. For example, the iron content of the oil can be determined using ASTM D 5185.

(210) The oil can, for example, have a phosphorus content of 25 ppm or less (e.g., 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of phosphorus. The phosphorus content of the oil can be determined using any suitable method, such as those known in the art. For example, the phosphorus content of the oil can be determined using ASTM D 5185.

(211) The oil can, for example, have a sulfur content of 250 ppm or less (e.g., 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50

ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of sulfur. The sulfur content of the oil can be determined by any suitable method, such as those known in the art. For example, the sulfur content of the oil can be determined using ASTM D 4294.

(212) The oil can, for example, have a calcium content of 50 ppm or less (e.g., 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of calcium. The calcium content of the oil can be determined using any suitable methods, such as those known in the art. In some examples, the calcium content of the oil can be determined using ASTM D 5185.

(213) The oil can, for example, have a copper content of 10 ppm or less (e.g., 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of copper. The copper content of the oil can be determined using any suitable method, such as those known in the art. For example, the copper content of the oil can be determined using ASTM D 5185.

(214) The oil can, for example, have a nickel content of 250 ppm or less (e.g., 225 ppm or less, 200 ppm or less, 175 ppm or less, 150 ppm or less, 125 ppm or less, 100 ppm or less, 75 ppm or less, 50 ppm or less, 45 ppm or less, 40 ppm or less, 35 ppm or less, 30 ppm or less, 25 ppm or less, 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of nickel. The nickel content of the oil can be determined using any suitable method, such as those known in the art. For example, the nickel content of the oil can be determined using ASTM D 5185.

(215) The oil can, for example, have a vanadium content of 25 ppm or less (e.g., 20 ppm or less, 15 ppm or less, 10 ppm or less, 9 ppm or less, 8 ppm or less, 7 ppm or less, 6 ppm or less, 5 ppm or less, 4.5 ppm or less, 4 ppm or less, 3.5 ppm or less, 3 ppm or less, 2.5 ppm or less, 2 ppm or less, 1.5 ppm or less, 1 ppm or less, 0.75 ppm or less, 0.5 ppm or less, 0.25 ppm or less, 0.1 ppm or less, 0.075 ppm or less, 0.05 ppm or less, 0.025 ppm or less, 0.01 ppm or less, 0.0075 ppm or less, or 0.005 ppm or less). In some examples, the oil can be substantially free of vanadium. The vanadium content of the oil can be determined using any suitable method, such as those known in the art. For example, the vanadium content of the oil can be determined using ASTM D 5185.

(216) In some examples, the oil has a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; and a silicon content of 2,000 ppm or less. In some examples, the oil has a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 2,000 ppm or less; and a sodium content of 100 ppm or less. In some examples, the oil has a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 2,000 ppm or less; a sodium content of 100 ppm or less; an iron content of 10 ppm or less; a sulfur content of 250 ppm or less; and a calcium content of 50 ppm or less. In some examples, the oil has

a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 2,000 ppm or less; a sodium content of 100 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 25 ppm or less; a sulfur content of 250 ppm or less; and a calcium content of 50 ppm or less. In some examples, the oil has a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 2,000 ppm or less; a sodium content of 100 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 25 ppm or less; a sulfur content of 250 ppm or less; a calcium content of 50 ppm or less; a copper content of 10 ppm or less; a nickel content of 250 ppm or less; and a vanadium content of 25 ppm or less.

(217) In some examples, the oil has a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; and a silicon content of 250 ppm or less. In some examples, the oil has a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 250 ppm or less; and a sodium content of 25 ppm or less. In some examples, the oil has a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 250 ppm or less; a sodium content of 25 ppm or less; an iron content of 10 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less. In some examples, the oil has: a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 250 ppm or less; a sodium content of 25 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 10 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less. In some examples, the oil has a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 250 ppm or less; a sodium content of 25 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 10 ppm or less; a sulfur content of 10 ppm or less; a calcium content of 5 ppm or less; a copper content of 1 ppm or less; a nickel content of 50 ppm or less; and a vanadium content of 1 ppm or less.

(218) The oil can, for example, have a Reid Vapor Pressure of 12.5 psig or less (e.g., 12 psig or less, 11.5 psig or less, 11 psig or less, 10.5 psig or less, 10 psig or less, 9.5 psig or less, 9 psig or less, 8.5 psig or less, 8 psig or less, 7.5 psig or less, 7 psig or less, 6.5 psig or less, 6 psig or less, 5.5 psig or less, 5 psig or less, 4.5 psig or less, 4 psig or less, 3.5 psig or less, 3 psig or less, or 2.5 psig or less). In some examples, the oil can have a Reid Vapor Pressure of 2 psig or more (e.g., 2.5 psig or more, 3 psig or more, 3.5 psig or more, 4 psig or more, 4.5 psig or more, 5 psig or more, 5.5 psig or more, 6 psig or more, 6.5 psig or more, 7 psig or more, 7.5 psig or more, 8 psig or more, 8.5 psig or more, 9 psig or more, 9.5 psig or more, 10 psig or more, 10.5 psig or more, or 11 psig or more). The Reid Vapor Pressure of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a Reid Vapor Pressure of from 2 to 12.5 psig (e.g., from 5 to 7 psig, from 7 to 12.5 psig, from 2 to 4 psig, from 4 to 6 psig, from 6 to 8 psig, from 8 to 10 psig, from 10 to 12.5 psig, from 2 to 12 psig, from 2 to 11 psig, from 2 to 10 psig, from 2 to 9 psig, from 2 to 8 psig, from 2 to 6 psig, from 2 to 5 psig, from 3 to 12.5 psig, from 4 to 12.5 psig, from 5 to 12.5 psig, from 6 to 12.5 psig, from 7 to 12.5 psig, from 8 to 12.5 psig, from 9 to 12.5 psig, from 3 to 12 psig, from 5 to 11 psig, or from 7 to 10 psig). The Reid Vapor Pressure of the oil can be determined using any suitable method, such as those known in the art. For example, the Reid Vapor Pressure of the oil can be determined using ASTM D 5191.

(219) The oil can, for example, have a water by distillation amount of 0.5 vol. % or less (e.g., 0.45 vol. % or less, 0.4 vol. % or less, 0.35 vol. % or less, 0.3 vol. % or less, 0.25 vol. % or less, 0.2 vol. % or less, 0.15 vol. % or less, 0.1 vol. % or less, 0.075 vol. % or less, 0.05 vol. % or less, 0.025 vol. % or less, or 0.01 vol. % or less). In some examples, the oil can have a water by distillation amount of 0 vol. % or more (e.g., 0.01 vol. % or more, 0.025 vol. % or more, 0.05 vol. % or more, 0.075 vol. % or more, 0.1 vol. % or more, 0.15 vol. % or more, 0.2 vol. % or more, 0.25 vol. % or more, 0.3 vol. % or more, 0.35 vol. % or more, or 0.4 vol. % or more).

(220) The amount of water by distillation in the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a water by distillation amount of from 0 to 0.5 vol. % (e.g., from 0 to 0.25 vol. %, from 0.25 to 0.5

vol. %, from 0 to 0.1 vol. %, from 0.1 to 0.2 vol. %, from 0.2 to 0.3 vol. %, from 0.3 to 0.4 vol. %, from 0.4 to 0.5 vol. %, from 0 to 0.4 vol. %, from 0 to 0.3 vol. %, from 0 to 0.2 vol. %, from 0 to 0.05 vol. %, or from 0 to 0.01 vol. %). The amount of water by distillation in the oil can be determined by any suitable method, such as those known in the art. For example, the water by distillation amount in the oil can be determined using ASTM D 95.

(221) The oil can, for example, have a total sediment content of 0.5 vol. % or less (e.g., 0.45 vol. % or less, 0.4 vol. % or less, 0.35 vol. % or less, 0.3 vol. % or less, 0.25 vol. % or less, 0.2 vol. % or less, 0.15 vol. % or less, 0.1 vol. % or less, 0.075 vol. % or less, 0.05 vol. % or less, 0.025 vol. % or less, or 0.01 vol. % or less). In some examples, the oil can have a total sediment content of 0 vol. % or more (e.g., 0.01 vol. % or more, 0.025 vol. % or more, 0.05 vol. % or more, 0.075 vol. % or more, 0.1 vol. % or more, 0.15 vol. % or more, 0.2 vol. % or more, 0.25 vol. % or more, 0.3 vol. % or more, 0.35 vol. % or more, or 0.4 vol. % or more). The total sediment content of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a total sediment content of from 0 to 0.5 vol. % (e.g., from 0 to 0.25 vol. %, from 0.25 to 0.5 vol. %, from 0 to 0.1 vol. %, from 0.1 to 0.2 vol. %, from 0.2 to 0.3 vol. %, from 0.3 to 0.4 vol. %, from 0.4 to 0.5 vol. %, from 0 to 0.4 vol. %, from 0 to 0.3 vol. %, from 0 to 0.2 vol. %, from 0 to 0.05 vol. %, or from 0 to 0.01 vol. %). The total sediment content of the oil can be determined by any suitable method, such as those known in the art. For example, the total sediment content of the oil can be determined using ASTM D 4870.

(222) The oil can, for example, have an n-heptane insoluble content of 0.1 wt. % or less (e.g., 0.09 wt. % or less, 0.08 wt. % or less, 0.07 wt. % or less, 0.06 wt. % or less, 0.05 wt. % or less, 0.04 wt. % or less, 0.03 wt. % or less, 0.02 wt. % or less, or 0.01 wt. % or less). In some examples, the oil can have an n-heptane insoluble content of 0 wt. % or more (e.g., 0.01 wt. % or more, 0.02 wt. % or more, 0.03 wt. % or more, 0.04 wt. % or more, 0.05 wt. % or more, 0.06 wt. % or more, 0.07 wt. % or more, or 0.08 wt. % or more). The n-heptane insoluble content of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have an n-heptane insoluble content of from 0 to 0.1 wt. % (e.g., from 0 to 0.05 wt. %, from 0.05 to 0.1 wt. %, from 0 to 0.02 wt. %, from 0.02 to 0.04 wt. %, from 0.04 to 0.06 wt. %, from 0.06 to 0.08 wt. %, from 0.08 to 0.1 wt. %, from 0 to 0.09 wt. %, from 0 to 0.08 wt. %, from 0 to 0.07 wt. %, from 0 to 0.06 wt. %, from 0 to 0.04 wt. %, from 0 to 0.03 wt. %, or from 0 to 0.01 wt. %). The n-heptane insoluble content of the oil can be determined using any suitable method, such as those known in the art. For example, the n-heptane insoluble content of the oil can be determined using ASTM D 3279.

(223) The oil can, for example, have a total acid number of 1 mg KOH/g or less (e.g., 0.9 mg KOH/g or less, 0.8 mg KOH/g or less, 0.7 mg KOH/g or less, 0.6 mg KOH/g or less, 0.5 mg KOH/g or less, 0.4 mg KOH/g or less, 0.3 mg KOH/g or less, 0.2 mg KOH/g or less, or 0.1 mg KOH/g or less). In some examples, the oil can have a total acid number of 0 mg KOH/g or more (e.g., 0.1 mg KOH/g or more, 0.2 mg KOH/g or more, 0.3 mg KOH/g or more, 0.4 mg KOH/g or more, 0.5 mg KOH/g or more, 0.6 mg KOH/g or more, 0.7 mg KOH/g or more, 0.8 mg KOH/g or more, or 0.9 mg KOH/g or more). The total acid number of the oil can range from any of the minimum values described above to any of the maximum values described above. For example, the oil can have a total acid number of from 0 to 1 mg KOH/g (e.g., from 0 to 0.5 mg KOH/g, from 0.5 to 1 mg KOH/g, from 0 to 0.2 mg KOH/g, from 0.2 to 0.4 mg KOH/g, from 0.4 to 0.6 mg KOH/g, from 0.6 to 0.8 mg KOH/g, from 0.8 to 1 mg KOH/g, from 0 to 0.8 mg KOH/g, from 0 to 0.6 mg KOH/g, from 0 to 0.4 mg KOH/g, or from 0 to 0.1 mg KOH/g). The total acid number of the oil can be determined using any suitable method, such as those known in the art. For example, the total acid number of the oil can be determined using ASTM D 664.

(224) In some examples, the oil has a Reid Vapor Pressure of 12.5 psig or less; and a final boiling point of 750° F. to 1,000° F. In some examples, the oil has a Reid Vapor Pressure of from 7 to 10 psig; and a final boiling point of from 935° F. to 950° F.

(225) In some examples, the oil has a Reid Vapor Pressure of 12.5 psig or less; and a pour point of 0° F. to 20° F. In some examples, the oil has a Reid Vapor Pressure of from 7 to 10 psig; and a pour point of from 10° F. to 15° F.

(226) In some examples, the oil has a final boiling point of 750° F. to 1,000° F.; and a pour point of 0° F. to 20° F. In some examples, the oil has a final boiling point of from 935° F. to 950° F.; and a pour point of from 10° F. to 15° F.

(227) In some examples, the oil has a Reid Vapor Pressure of 12.5 psig or less; a final boiling point of 750° F. to 1,000° F.; and a pour point of 0° F. to 20° F. In some examples, the oil has a Reid Vapor Pressure of from 7 to 10 psig; a final boiling point of from 935° F. to 950° F.; and a pour point of from 10° F. to 15° F.;

(228) In some examples, the oil has a Reid Vapor Pressure of 12.5 psig or less; a final boiling point of 750° F. to 1,000° F.; a pour point of 0° F. to 20° F.; a total chloride content of 500 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 2,000 ppm or less; a sodium content of 100 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 25 ppm or less; a sulfur content of 250 ppm or less; and a calcium content of 50 ppm or less. In some examples, the oil has a Reid Vapor Pressure of from 7 to 10 psig; a final boiling point of from 935° F. to 950° F.; a pour point of from 10° F. to 15° F.; a total chloride content of 100 ppm or less; a nitrogen content of 600 ppm or less; a silicon content of 250 ppm or less; a sodium content of 25 ppm or less; an iron content of 10 ppm or less; a phosphorus content of 10 ppm or less; a sulfur content of 10 ppm or less; and a calcium content of 5 ppm or less.

(229) In some examples, the oil is a raw pyrolysis product, meaning the oil is produced by a method that substantially excludes any hydrotreatment or further refining steps after pyrolysis.

Compositions Comprising the Oil and the Wax, Such as Blends

(230) Also disclosed herein are compositions comprising any of waxes disclosed herein and any of the oils disclosed herein.

(231) For example, the composition can comprise 50% or more of the oil by volume (e.g., 51% or more, 52% or more, 53% or more, 54% or more, 55% or more, 56% or more, 57% or more, 58% or more, 59% or more, 60% or more, 61% or more, 62% or more, 63% or more, 64% or more, 65% or more, 66% or more, 67% or more, 68% or more, or 69% or more). In some examples, the composition can comprise 70% or less of the oil by volume (e.g., 69% or less, 68% or less, 67% or less, 66% or less, 65% or less, 64% or less, 63% or less, 62% or less, 61% or less, 60% or less, 59% or less, 58% or less, 57% or less, 56% or less, 55% or less, 54% or less, 53% or less, 52% or less, or 51% or less). The amount of oil by volume in the composition can range from any of the minimum values described above to any of the maximum values described above. For example, the composition can comprise from 50% to 70% of the oil by volume (e.g., from 50% to 60%, from 60% to 70%, from 50% to 55%, from 55% to 60%, from 60% to 65%, from 65% to 70%, from 50% to 65%, from 55% to 70%, or from 55% to 65%).

(232) In some examples, the composition can comprise 30% or more of the wax by volume (e.g., 31% or more, 32% or more, 33% or more, 34% or more, 35% or more, 36% or more, 37% or more, 38% or more, 39% or more, 40% or more, 41% or more, 42% or more, 43% or more, 44% or more, 45% or more, 46% or more, 47% or more, 48% or more, or 49% or more). In some examples, the composition can comprise 50% or less of the wax by volume (e.g., 49% or less, 48% or less, 47% or less, 46% or less, 45% or less, 44% or less, 43% or less, 42% or less, 41% or less, 40% or less, 39% or less, 38% or less, 37% or less, 36% or less, 35% or less, 34% or less, 33% or less, 32% or less, or 31% or less). The amount of wax by volume in the composition can range from any of the minimum values described above to any of the maximum values described above. For example, the composition can comprise from 30% to 50% of the wax by volume (e.g., from 30% to 40%, from 40% to 50%, from 30% to 35%, from 35% to 40%, from 40% to 45%, from 45% to 50%, from 30% to 45%, from 35% to 50%, or from 35% to 45%).

(233) For example, the composition can comprise 50-70% of the oil and 30-50% of the wax by

volume. For example, the composition can comprise 65% oil and 35% wax by volume. In some examples, the composition comprises 50% oil and 50% wax by volume. In some examples, the composition comprises a blend of the wax and the oil.

(234) Systems and Methods of Making

(235) Also disclosed herein are methods of making any of the compositions (e.g., waxes, oil, blends, etc.) described herein.

(236) For example, disclosed herein are systems and methods for making hydrocarbon based compositions derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics, such as any of the compositions described herein above. In some examples, the compositions disclosed herein can comprise a wax, an oil, or a combination thereof.

(237) Recycling of plastics via pyrolysis is a technology that generates products with a broad range of quality dependent upon a variety of factors, including the feedstock and manufacturing process. Pyrolysis depolymerizes plastics into products comprised of building block molecules.

Contaminants are introduced during plastic formulation and manufacturing processes during the first life of plastic in conjunction with the source and collection method of the plastics.

(238) For example, described herein are systems and methods for plastic to liquids conversion that can accept, for example, polyethylene, polypropylene, and/or polystyrene plastics that are neither suitable nor desirable for conventional (mechanical) plastic recycling. The plastic is thermally converted to liquid (e.g., oil) and wax hydrocarbon products. The hydrocarbon products can, for example, be used in the production of new plastics through conventional hydrocarbon cracking units. The hydrocarbon products can, for example, also be used as an alternative for naphtha, fuel, etc. The systems and methods herein can also produce char/coke and combustible gases, e.g. as products or byproducts.

(239) Plastics that are typically received would have otherwise been destined for disposal at a landfill or waste to energy plant because of their physical form and/or make-up prevents them from being effectively recycled by current conventional (mechanical) recycling means. Most film plastics fall into this category, as do others that have intermixed types of plastic resins or simply have contaminants (such as paper labels, organic food residue, functional additives, colorants, etc.) that make conventional (mechanical) recycling uneconomical.

(240) The systems and/or methods described herein can, for example, operate on an industrial scale.

(241) In some examples, the systems and/or methods described herein can process 5 metric tons or more of plastic feedstock per day (e.g., 5.5 metric tons or more, 6 metric tons or more, 6.5 metric tons or more, 7 metric tons or more, 7.5 metric tons or more, 8 metric tons or more, 8.5 metric tons or more, 9 metric tons or more, 9.5 metric tons or more, 10 metric tons or more, 11 metric tons or more, 12 metric tons or more, 13 metric tons or more, 14 metric tons or more, 15 metric tons or more, 20 metric tons or more, 25 metric tons or more, 30 metric tons or more, 35 metric tons or more, 40 metric tons or more, 45 metric tons or more, 50 metric tons or more, 60 metric tons or more, 70 metric tons or more, 80 metric tons or more, 90 metric tons or more, 100 metric tons or more, 125 metric tons or more, 150 metric tons or more, 175 metric tons or more, 200 metric tons or more, 225 metric tons or more, 250 metric tons or more, 300 metric tons or more, 350 metric tons or more, 400 metric tons or more, 450 metric tons or more, 500 metric tons or more, 600 metric tons or more, 700 metric tons or more, 800 metric tons or more, or 900 metric tons or more). In some examples, the systems and methods described herein can process 1,000 metric tons or less of plastic feedstock per day (e.g., 900 metric tons or less, 800 metric tons or less, 700 metric tons or less, 600 metric tons or less, 500 metric tons or less, 450 metric tons or less, 400 metric tons or less, 350 metric tons or less, 300 metric tons or less, 250 metric tons or less, 225 metric tons or less, 200 metric tons or less, 175 metric tons or less, 150 metric tons or less, 125 metric tons or less, 100 metric tons or less, 90 metric tons or less, 80 metric tons or less, 70 metric tons or less, 60 metric tons or less, 50 metric tons or less, 45 metric tons or less, 40 metric tons or less, 35 metric

tons or less, 30 metric tons or less, 25 metric tons or less, 20 metric tons or less, 15 metric tons or less, 14 metric tons or less, 13 metric tons or less, 12 metric tons or less, 11 metric tons or less, 10 metric tons or less, 9.5 metric tons or less, 9 metric tons or less, 8.5 metric tons or less, 8 metric tons or less, 7.5 metric tons or less, 7 metric tons or less, 6.5 metric tons or less, or 6 metric tons or less). The amount of plastic feedstock processed by the systems and/or methods herein can range from any of the minimum values described above to any of the maximum values described above. For example, the systems and/or methods described herein can process from 5 to 1,000 metric tons of plastic feedstock per day (e.g., from 5 to 500 metric tons, from 500 to 1,000 metric tons, from 5 to 200 metric tons, from 200 to 400 metric tons, from 400 to 600 metric tons, from 600 to 800 metric tons, from 800 to 1,000 metric tons, from 5 to 800 metric tons, from 5 to 600 metric tons, from 5 to 400 metric tons, from 5 to 100 metric tons, from 5 to 50 metric tons, from 5 to 25 metric tons, from 10 to 1,000 metric tons, from 25 to 1,000 metric tons, from 50 to 1,000 metric tons, from 100 to 1,000 metric tons, from 200 to 1,000 metric tons, from 400 to 1,000 metric tons, from 600 to 1,000 metric tons, from 10 to 900 metric tons, from 15 to 800 metric tons, from 25 to 750 metric tons, or from 50 to 500 metric tons).

(242) In some examples, the systems and/or methods described herein can produce 10,000 gallons of pyrolysis product (e.g., oil and/or wax, etc.) or more in an amount of time (e.g., 11,000 gallons or more, 12,000 gallons or more, 13,000 gallons or more, 14,000 gallons or more, 15,000 gallons or more, 20,000 gallons or more, 25,000 gallons or more, 30,000 gallons or more, 35,000 gallons or more, 40,000 gallons or more, 45,000 gallons or more, 50,000 gallons or more, 60,000 gallons or more, 70,000 gallons or more, 80,000 gallons or more, 90,000 gallons or more, 100,000 gallons or more, 125,000 gallons or more, 150,000 gallons or more, 175,000 gallons or more, 200,000 gallons or more, 225,000 gallons or more, 250,000 gallons or more, 300,000 gallons or more, 350,000 gallons or more, 400,000 gallons or more, 450,000 gallons or more, 500,000 gallons or more, 600,000 gallons or more, 700,000 gallons or more, 800,000 gallons or more, or 900,000 gallons or more). In some examples, the systems and/or methods described herein can produce 1,000,000 gallons of pyrolysis product (e.g., oil and/or wax, etc.) or more in an amount of time (e.g., 900,000 gallons or less, 800,000 gallons or less, 700,000 gallons or less, 600,000 gallons or less, 500,000 gallons or less, 450,000 gallons or less, 400,000 gallons or less, 350,000 gallons or less, 300,000 gallons or less, 250,000 gallons or less, 225,000 gallons or less, 200,000 gallons or less, 175,000 gallons or less, 150,000 gallons or less, 125,000 gallons or less, 100,000 gallons or less, 90,000 gallons or less, 80,000 gallons or less, 70,000 gallons or less, 60,000 gallons or less, 50,000 gallons or less, 45,000 gallons or less, 40,000 gallons or less, 35,000 gallons or less, 30,000 gallons or less, 25,000 gallons or less, 20,000 gallons or less, 15,000 gallons or less, 14,000 gallons or less, 13,000 gallons or less, or 12,000 gallons or less). The amount of pyrolysis product produced in the amount of time by the systems and/or methods described herein can range from any of the minimum values described above to any of the maximum values described above. For example, the systems and/or methods described herein can produce from 10,000 to 1,000,000 gallons of pyrolysis product (e.g., oil and/or wax, etc.) or more in an amount of time (e.g., from 10,000 to 500,000 gallons, from 500,000 to 1,000,000 gallons, from 10,000 to 200,000 gallons, from 200,000 to 400,000 gallons, from 400,000 to 600,000 gallons, from 600,000 to 800,000 gallons, from 800,000 to 1,000,000 gallons, from 10,000 to 800,000 gallons, from 10,000 to 600,000 gallons, from 10,000 to 400,000 gallons, from 10,000 to 200,000 gallons, from 10,000 to 100,000 gallons, from 10,000 to 50,000 gallons, from 10,000 to 25,000 gallons, from 25,000 to 1,000,000 gallons, from 50,000 to 1,000,000 gallons, from 100,000 to 1,000,000 gallons, from 200,000 to 1,000,000 gallons, from 400,000 to 1,000,000 gallons, from 600,000 to 1,000,000 gallons, from 15,000 to 900,000 gallons, or from 20,000 to 800,000 gallons).

(243) The amount of time in which the pyrolysis product is produced by the systems and/or methods can, for example, be 5 days or more (e.g., 6 days or more, 7 days or more, 8 days or more, 9 days or more, 10 days or more, 11 days or more, 12 days or more, 13 days or more, 14 days or

more, 15 days or more, 16 days or more, 17 days or more, 18 days or more, 19 days or more, 20 days or more, 21 days or more, 22 days or more, 23 days or more, 24 days or more, 25 days or more, 26 days or more, 27 days or more, 28 days or more, 29 days or more, 30 days or more, 35 days or more, 40 days or more, 45 days or more, 50 days or more, 60 days or more, 70 days or more, or 80 days or more). In some examples, the amount of time in which the pyrolysis product is produced by the systems and/or methods can be 90 days or less (e.g., 80 days or less, 70 days or less, 60 days or less, 50 days or less, 45 days or less, 40 days or less, 35 days or less, 30 days or less, 29 days or less, 28 days or less, 27 days or less, 26 days or less, 25 days or less, 24 days or less, 23 days or less, 22 days or less, 21 days or less, 20 days or less, 19 days or less, 18 days or less, 17 days or less, 16 days or less, 15 days or less, 14 days or less, 13 days or less, 12 days or less, 11 days or less, 10 days or less, 9 days or less, 8 days or less, or 7 days or less). The amount of time in which the pyrolysis product is produced by the systems and/or methods can range from any of the minimum values described above to any of the maximum values described above. For example, the amount of time in which the pyrolysis product is produced by the systems and/or methods can be from 5 to 90 days (e.g., from 4 to 45 days, from 45 to 90 days, from 5 to 30 days, from 30 to 60 days, from 60 to 90 days, from 5 to 80 days, from 5 to 70 days, from 5 to 60 days, from 5 to 50 days, from 5 to 40 days, from 5 to 21 days, from 5 to 14 days, from 5 to 10 days, from 7 to 90 days, from 10 to 90 days, from 14 to 90 days, from 21 to 90 days, from 30 to 90 days, from 40 to 90 days, from 50 to 90 days, from 70 to 90 days, from 7 to 80 days, or from 10 to 60 days).

(244) In some examples, the systems and/or methods described herein can process from 5 to 1,000 metric tons per day of plastic feedstock and produce from 10,000 to 1,000,000 gallons of pyrolysis product (e.g., oil, wax, or a combination thereof) per 5 to 90 days.

(245) FIG. 1-FIG. 5 are block flow diagrams of example systems and methods described herein.

(246) The systems and methods can, for example, include intake of plastic feedstock, sorting and/or reducing the size of the plastic feedstock, followed by pyrolysis and/or removal of contaminants to produce the hydrocarbon product, which can optionally be post-treated.

(247) Feedstock

(248) The feedstock comprises post-consumer and/or post-industrial plastics. “Post-industrial” or “Pre-consumer” plastics include materials derived from waste streams during a plastic manufacturing process. “Post-consumer” plastics include materials generated by households or by commercial, industrial, and/or institutional facilities in their roles as end-users of the product which can no longer be used for its intended purpose. This includes returns of material from the distribution chain.

(249) In some examples, the feedstock comprises 50% or more by weight post-consumer plastics (e.g., 51% or more, 52% or more, 53% or more, 54% or more, 55% or more, 56% or more, 57% or more, 58% or more, 59% or more, 60% or more, 61% or more, 62% or more, 63% or more, 64% or more, 65% or more, 66% or more, 67% or more, 68% or more, 69% or more, 70% or more, 71% or more, 72% or more, 73% or more, 74% or more, 75% or more, 76% or more, 77% or more, 78% or more, 79% or more, 80% or more, 81% or more, 82% or more, 83% or more, 84% or more, 85% or more, 86% or more, 87% or more, 88% or more, 89% or more, 90% or more, 91% or more, 92% or more, 93% or more, 94% or more, 95% or more, 96% or more, 97% or more, 98% or more, or 99% or more). In some examples, the feedstock comprises 100% or less by weight post-consumer plastics (e.g., 99% or less, 98% or less, 97% or less, 96% or less, 95% or less, 94% or less, 93% or less, 92% or less, 91% or less, 90% or less, 89% or less, 88% or less, 87% or less, 86% or less, 85% or less, 84% or less, 83% or less, 82% or less, 81% or less, 80% or less, 79% or less, 78% or less, 77% or less, 76% or less, 75% or less, 74% or less, 73% or less, 72% or less, 71% or less, 70% or less, 69% or less, 68% or less, 67% or less, 66% or less, 65% or less, 64% or less, 63% or less, 62% or less, 61% or less, 60% or less, 59% or less, 58% or less, 57% or less, 56% or less, 55% or less, 54% or less, 53% or less, or 52% or less). The percent by weight of the feedstock that is post-consumer plastics can range from any of the minimum values described above to any of the

maximum values described above. For example, the feedstock can comprise from 50% to 100% by weight post-consumer plastics (e.g., from 50% to 75%, from 75% to 100%, from 50% to 60%, from 60% to 70%, from 70% to 80%, from 80% to 90%, from 90 to 100%, from 50 to 99%, from 50 to 95%, from 50 to 90%, from 50% to 80%, from 50% to 70%, from 55% to 100%, from 60% to 100%, from 70% to 100%, from 75 to 100%, from 80 to 100%, from 95 to 100%, from 55% to 99%, from 70% to 99%, or from 75 to 95%).

(250) Plastic feedstock can be provided in any suitable form, such as, for example, loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, etc. In some examples, the feedstock comprises films, such as single and/or multi-layered films.

(251) In some examples, the plastic feedstock can be packaged, e.g. in bales, boxes, drums, etc.

(252) The feedstock can, for example, comprise polyethylene (e.g., LDPE, LLDPE, VLDPE, MDPE, HDPE, UHMWPE, PEX, etc.), polypropylene, polystyrene, or a combination thereof. In some examples, the feedstock includes plastics with a plastic type classification #2, 4, 5, 6, or a combination thereof.

(253) In some examples, a majority of the plastic that is processed by the systems and methods described herein comprises low-density or linear-low density polyethylene (LDPE—#4) and high-density polyethylene (HDPE—#2), in particular film plastic, and the systems and methods described herein are optimized to effectively process these materials.

(254) A substantial portion of polyethylene and polypropylene polymers are used in single use plastics and get discarded after its use. Polyethylene is used widely in various consumer and industrial products. Polyethylene is the most common plastic, over 100 million tons of polyethylene resins are produced annually. Its primary use is in packaging (plastic bags, plastic films, geomembranes, containers including bottles, etc.). Polyethylene is produced in a variety of forms (e.g., ultra-high molecular weight polyethylene (UHMWPE), high-density polyethylene (HDPE), medium density polyethylene (MDPE), linear low-density polyethylene (LLDPE), low-density polyethylene (LDPE), very low density polyethylene (VLDPE), crosslinked polyethylene (PEX)) with the same chemical formula (C.sub.2H.sub.4).sub.n but different molecular structure. HDPE has a low degree of branching with short side chains while LDPE has a very high degree of branching with long side chains. LLDPE is a substantially linear polymer with significant numbers of short branches, commonly made by copolymerization of ethylene with short-chain alpha-olefins.

(255) The feedstock can, for example, comprise polyethylene, polypropylene, polystyrene, or a combination thereof in an amount of 90% or more by weight (e.g., 91% or more, 92% or more, 93% or more, 94% or more, 95% or more, 96% or more, 97% or more, 98% or more, or 99% or more). In some examples, the feedstock comprises polyethylene, polypropylene, polystyrene, or a combination thereof in an amount of 100% or less by weight (e.g., 99% or less, 98% or less, 97% or less, 96% or less, 95% or less, 94% or less, 93% or less, 92% or less, or 91% or less). The amount of polyethylene, polypropylene, polystyrene, or a combination thereof in the feedstock can range from any of the minimum values described above to any of the maximum values described above. For example, the feedstock can comprise polyethylene, polypropylene, polystyrene, or a combination thereof in an amount of from 90% to 100% by weight (e.g., from 90% to 95%, from 95% to 100%, from 90% to 92%, from 92% to 94%, from 94% to 96%, from 96% to 98%, from 98% to 100%, from 90% to 98%, from 90% to 96%, from 90% to 94%, from 92% to 100%, from 94% to 100%, from 96% to 100%, from 91% to 99%, from 92% to 98%, or from 93% to 97%).

(256) In some examples, the feedstock comprises moisture (e.g., water) in an amount of 20% or less by weight (e.g., 19.5% or less, 19% or less, 18.5% or less, 18% or less, 17.5% or less, 17% or less, 16.5% or less, 16% or less, 15.5% or less, 15% or less, 14.5% or less, 14% or less, 13.5% or less, 13% or less, 12.5% or less, 12% or less, 11.5% or less, 11% or less, 10.5% or less, 10% or less, 9.5% or less, 9% or less, 8.5% or less, 8% or less, 7.5% or less, 7% or less, 6.5% or less, 6% or less, 5.5% or less, 5% or less, 4.5% or less, 4% or less, 3.5% or less, 3% or less, 2.5% or less,

2% or less, 1.5% or less, 1% or less, or 0.5% or less). In some examples, the feedstock comprises moisture in an amount of 0% or more by weight (e.g., 0.5% or more, 1% or more, 1.5% or more, 2% or more, 2.5% or more, 3% or more, 3.5% or more, 4% or more, 4.5% or more, 5% or more, 5.5% or more, 6% or more, 6.5% or more, 7% or more, 7.5% or more, 8% or more, 8.5% or more, 9% or more, 9.5% or more, 10% or more, 10.5% or more, 11% or more, 11.5% or more, 12% or more, 12.5% or more, 13% or more, 13.5% or more, 14% or more, 14.5% or more, 15% or more, 15.5% or more, 16% or more, 16.5% or more, 17% or more, 17.5% or more, 18% or more, 18.5% or more, or 19% or more). The amount of moisture in the feedstock can range from any of the minimum values described above to any of the maximum values described above. For example, the feedstock can comprise moisture in an amount of from 0% to 20% by weight (e.g., from 0% to 10%, from 10% to 20%, from 0% to 5%, from 5% to 10%, from 5% to 15%, from 15% to 20%, from 0% to 2.5%, from 2.5% to 5%, from 5% to 7.5%, from 7.5% to 10%, from 10% to 12.5%, from 12.5% to 15%, from 15% to 17.5%, from 17.5% to 20%, from 0% to 19%, from 0% to 18%, from 0% to 17%, from 0% to 16%, from 0% to 15%, from 0% to 14%, from 0% to 13%, from 0% to 12%, from 0% to 11%, from 0% to 9%, from 0% to 8%, from 0% to 7%, from 0% to 6%, from 0% to 4%, from 0% to 3%, from 0% to 2%, from 0% to 1%, from 1% to 20%, from 2% to 20%, from 3% to 20%, from 4% to 20%, from 6% to 20%, from 7% to 20%, from 8% to 20%, from 9% to 20%, from 11% to 20%, from 12% to 20%, from 13% to 20%, from 14% to 20%, from 16% to 20%, from 17% to 20%, from 18% to 20%, from 0.5% to 19.5%, from 1% to 19%, from 1% to 15%, from 1% to 10%, or from 1% to 5%).

(257) Polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyethylene terephthalate (PET) (commonly used for plastic bottles), nylon, ethylene vinyl alcohol (EVOH), polycarbonate (PC), acrylonitrile butadiene styrene (ABS), rubber, thermosets, and non-plastic components (e.g., metal, glass, wood, cotton, paper, cardboard, dirt, inorganics, etc.) are not desirable and their presence should be minimized.

(258) In some examples, the feedstock comprises 5% or less by weight polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyethylene terephthalate (PET), nylon, ethylene vinyl alcohol (EVOH), polycarbonate (PC), acrylonitrile butadiene styrene (ABS), rubber, thermosets, or a combination thereof (e.g., 4.5% or less, 4% or less, 3.5% or less, 3% or less, 2.5% or less, 2% or less, 1.75% or less, 1.5% or less, 1.25% or less, 1% or less, 0.9% or less, 0.8% or less, 0.7% or less, 0.6% or less, 0.5% or less, 0.4% or less, 0.3% or less, 0.2% or less, or 0.1% or less). In some examples, the feedstock comprises 0% or more by weight polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyethylene terephthalate (PET), nylon, ethylene vinyl alcohol (EVOH), polycarbonate (PC), acrylonitrile butadiene styrene (ABS), rubber, thermosets, or a combination thereof (e.g., 0.1% or more, 0.2% or more, 0.3% or more, 0.4% or more, 0.5% or more, 0.6% or more, 0.7% or more, 0.8% or more, 0.9% or more, 1% or more, 1.25% or more, 1.5% or more, 1.75% or more, 2% or more, 2.5% or more, 3% or more, 3.5% or more, or 4% or more). The amount of polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyethylene terephthalate (PET), nylon, ethylene vinyl alcohol (EVOH), polycarbonate (PC), acrylonitrile butadiene styrene (ABS), rubber, thermosets, or a combination thereof in the feedstock can range from any of the minimum values described above to any of the maximum values described above. For example, the feedstock can comprise from 0% to 5% by weight polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyethylene terephthalate (PET), nylon, ethylene vinyl alcohol (EVOH), polycarbonate (PC), acrylonitrile butadiene styrene (ABS), rubber, thermosets, or a combination thereof (e.g., from 0% to 2.5%, from 2.5% to 5%, from 0% to 1%, from 1% to 2%, from 2% to 3%, from 3% to 4%, from 4% to 5%, from 0% to 4.5%, from 0% to 4%, from 0% to 3.5%, from 0% to 3%, from 0% to 2%, from 0% to 1.5%, from 0% to 0.5%, from 0.5% to 5%, from 1% to 5%, from 1.5% to 5%, from 2% to 5%, from 3% to 5%, from 3.5% to 5%, from 0.1% to 4.5%, from 0.2% to 4%, or from 0.3% to 3%).

(259) The feedstock can, for example, comprise 15% by weight or less non-plastic materials, such

as metal, glass, wood, cotton, paper, cardboard, dirt, inorganics, etc., or a combination thereof (e.g., 14.5% or less, 14% or less, 13.5% or less, 13% or less, 12.5% or less, 12% or less, 11.5% or less, 11% or less, 10.5% or less, 10% or less, 9.5% or less, 9% or less, 8.5% or less, 8% or less, 7.5% or less, 7% or less, 6.5% or less, 6% or less, 5.5% or less, 5% or less, 4.5% or less, 4% or less, 3.5% or less, 3% or less, 2.5% or less, 2% or less, 1.5% or less, 1% or less, or 0.5% or less). In some examples, the feedstock comprises 0% or more by weight non-plastic materials (e.g., 0.5% or more, 1% or more, 1.5% or more, 2% or more, 2.5% or more, 3% or more, 3.5% or more, 4% or more, 4.5% or more, 5% or more, 5.5% or more, 6% or more, 6.5% or more, 7% or more, 7.5% or more, 8% or more, 8.5% or more, 9% or more, 9.5% or more, 10% or more, 10.5% or more, 11% or more, 11.5% or more, 12% or more, 12.5% or more, 13% or more, 13.5% or more, or 14% or more). The amount of non-plastic materials in the feedstock can range from any of the minimum values described above to any of the maximum values described above. For example, the feedstock can comprise non-plastic materials in an amount of from 0% to 15% by weight (e.g., from 0% to 7.5%, from 7.5% to 15%, from 0% to 5%, from 5% to 10%, from 10% to 15%, from 0% to 2.5%, 2.5% to 5%, from 5% to 7.5%, from 7.5% to 10%, from 10% to 12.5%, from 12.5% to 15%, from 0% to 14%, from 0% to 13%, from 0% to 12%, from 0% to 11%, from 0% to 10%, from 0% to 9%, from 0% to 8%, from 0% to 7%, from 0% to 6%, from 0% to 4%, from 0% to 3%, from 0% to 2%, from 1% to 15%, from 2% to 15%, from 3% to 15%, from 4% to 15%, from 5% to 15%, from 6% to 15%, from 7% to 15%, from 8% to 15%, from 9% to 15%, from 11% to 15%, from 12% to 15%, from 15% to 15%, from 0.5% to 14.5%, from 1% to 14%, or from 1% to 10%).

(260) In some examples, the feedstock can initially be manually, visually, and/or automatically (e.g., by an automated system/component) checked to ensure it contains the correct material and does not contain an inordinate amount of obvious contamination. During the manual/visual/automated inspection of the feedstock, the feedstock is inspected for large contaminant items, such as metal, glass, PVC, paper, wood, PET plastics, and cardboard, which are removed when identified.

(261) In some examples, the feedstock can further be assessed, e.g. for chemical and/or physical properties. This can include, for example, assessing at least a representative sample portion of each feedstock via infrared analysis (e.g., portable infrared analyzer), gas chromatography-mass spectrometry (GC-MS), a bench-scale pyrolysis test, ASTM testing for specific contaminants and physical properties, melt-index test, ash test, or a combination thereof.

(262) Feedstock that fails to meet the initial inspection criteria is not further processed by the systems or methods described herein.

(263) After the initial inspection is complete, the acceptable feedstock can be stored for future use (e.g., in a stockpile, a hopper, etc.) and/or loaded into the system for processing.

(264) Infeed

(265) In some examples, the feedstock can be loaded into the system via an infeed conveyor. The rate at which the infeed conveyor provides feedstock to the system (e.g., the feed rate) can, for example, be 500 pounds per hour (lb./hr.) or more (e.g., 550 lb./hr. or more, 600 lb./hr. or more, 650 lb./hr. or more, 700 lb./hr. or more, 750 lb./hr. or more, 800 lb./hr. or more, 850 lb./hr. or more, 900 lb./hr. or more, 950 lb./hr. or more, 1,000 lb./hr. or more, 1,100 lb./hr. or more, 1,200 lb./hr. or more, 1,300 lb./hr. or more, 1,400 lb./hr. or more, 1,500 lb./hr. or more, 1,750 lb./hr. or more, 2,000 lb./hr. or more, 2,250 lb./hr. or more, 2,500 lb./hr. or more, 2,750 lb./hr. or more, 3,000 lb./hr. or more, 3,250 lb./hr. or more, 3,500 lb./hr. or more, 3,750 lb./hr. or more, 4,000 lb./hr. or more, 4,250 lb./hr. or more, 4,500 lb./hr. or more, 4,750 lb./hr. or more, 5,000 lb./hr. or more, 5,500 lb./hr. or more, 6,000 lb./hr. or more, 6,500 lb./hr. or more, 7,000 lb./hr. or more, 7,500 lb./hr. or more, 8,000 lb./hr. or more, 8,500 lb./hr. or more, 9,000 lb./hr. or more, 9,500 lb./hr. or more, 10,000 lb./hr. or more, 11,000 lb./hr. or more, 12,000 lb./hr. or more, 13,000 lb./hr. or more, 14,000 lb./hr. or more, 15,000 lb./hr. or more, 16,000 lb./hr. or more, 17,000 lb./hr. or more, 18,000 lb./hr. or more, or 19,000 lb./hr. or more). In some examples, the rate at which the infeed conveyor provides feedstock

to the system (e.g., the feed rate) can be 20,000 lb./hr. or less (e.g., 19,000 lb./hr. or less, 18,000 lb./hr. or less, 17,000 lb./hr. or less, 16,000 lb./hr. or less, 15,000 lb./hr. or less, 14,000 lb./hr. or less, 13,000 lb./hr. or less, 12,000 lb./hr. or less, 11,000 lb./hr. or less, 10,000 lb./hr. or less, 9,500 lb./hr. or less, 9,000 lb./hr. or less, 8,500 lb./hr. or less, 8,000 lb./hr. or less, 7,500 lb./hr. or less, 7,000 lb./hr. or less, 6,500 lb./hr. or less, 6,000 lb./hr. or less, 5,500 lb./hr. or less, 5,000 lb./hr. or less, 4,750 lb./hr. or less, 4,500 lb./hr. or less, 4,250 lb./hr. or less, 4,000 lb./hr. or less, 3,750 lb./hr. or less, 3,500 lb./hr. or less, 3,250 lb./hr. or less, 3,000 lb./hr. or less, 2,750 lb./hr. or less, 2,500 lb./hr. or less, 2,250 lb./hr. or less, 2,000 lb./hr. or less, 1,750 lb./hr. or less, 1,500 lb./hr. or less, 1,400 lb./hr. or less, 1,300 lb./hr. or less, 1,200 lb./hr. or less, 1,100 lb./hr. or less, 1,000 lb./hr. or less, 950 lb./hr. or less, 900 lb./hr. or less, 850 lb./hr. or less, 800 lb./hr. or less, 750 lb./hr. or less, 700 lb./hr. or less, 650 lb./hr. or less, or 600 lb./hr. or less). The rate at which the infeed conveyor provides feedstock to the system can range from any of the minimum values described above to any of the maximum values described above. For example, the rate at which the infeed conveyor provides feedstock to the system can be from 500 pounds per hour (lb./hr.) to 20,000 lb./hr. (e.g., from 500 to 5,000 lb./hr., from 5,000 to 20,000 lb./hr., from 500 to 4,000 lb./hr., from 4,000 to 8,000 lb./hr., from 8,000 to 12,000 lb./hr., from 12,000 to 16,000 lb./hr., from 16,000 to 20,000 lb./hr., from 500 to 15,000 lb./hr., from 500 to 10,000 lb./hr., from 500 to 9,000 lb./hr., from 500 to 8,000 lb./hr., from 500 to 7,000 lb./hr., from 500 to 6,000 lb./hr., from 500 to 2,500 lb./hr., from 1,000 to 20,000 lb./hr., from 2,500 to 20,000 lb./hr., from 6,000 to 20,000 lb./hr., from 7,000 to 20,000 lb./hr., from 8,000 to 20,000 lb./hr., from 9,000 to 20,000 lb./hr., from 10,000 to 20,000 lb./hr., from 550 to 19,000 lb./hr., from 600 to 19,000 lb./hr., or from 1,000 to 15,000 lb./hr.).

(266) Sorting

(267) In some examples, feedstock loaded into the system can undergo additional sorting.

(268) In some examples, the plastic feedstock can be deposited onto a conveyor and/or further processed to remove contaminants. This can, for example, include visual inspection and manual removal, automated inspection and removal, positioning one or more magnets to magnetically remove ferrous contaminants (e.g., various components such as nuts, bolts, screws, small pieces of wire, etc. comprising ferrous metals and/or alloys), washing and/or drying, size based separation (e.g., screening, sifting, etc.), air jets, sink float, etc.

(269) In some examples, the feedstock can be transported to a trommel, such as a screen trommel. The screen trommel can, for example, be used to remove fine dust, particles, and other contaminants from the incoming feedstock stream, for example before and/or after it has passed through a shredder. The trommel can receive feedstock and trommel rotation can agitate incoming feedstock and promote removal of granular materials (e.g., sand, pigment, binder, food particulates, dirt, etc.) in the feedstock through the trommel screen. The remaining oversized material from the trommel can be deposited, for example, onto a conveyor for further inspection and/or sorting.

(270) In some examples, visual inspection and manual sorting and/or automated inspection and sorting is used to remove contaminants from the plastic feedstock, e.g., before and/or after passing through the trommel and/or shredder. Contaminants to be removed can, for example, include undesirable plastic (such as PET, PVC, nylon, and thermosets) as well as other materials that can damage downstream equipment or degrade the quality of the finished products such as strapping, paper, cardboard, rope, batteries, beverage bottles still containing liquid, glass, wood, metal, electronics, and a wide range of other non-plastic materials.

(271) Size Reduction

(272) In some examples, feedstock loaded into the system can undergo one or more size reductions. The size reduction can be accomplished by any suitable means, such as those known in the art. For example, the feedstock can be shredded, pelletized, densified, or a combination thereof. For example, the system can include one or more size reduction components, such as a chipper, granulator, grinder, hammermill, shredder (e.g., a shear shredder), pelletizer, densifier, agglomerator, or a combination thereof.

(273) In some examples, the feedstock can be shredded, for example using one or more shredders. Each shredder can comprise any suitable type of shredder, such as those known in the art. In some examples, the system can include one or more shear shredders.

(274) The shredder can perform a size reduction on incoming plastic, for example to a range of 0.25 to 36 inches (longest dimension). For example, the shredder can reduce the average initial size of the incoming plastic to 0.25 inches or more (longest dimension) (e.g., 0.5 inches or more, 1 inch or more, 1.5 inches or more, 2 inches or more, 3 inches or more, 4 inches or more, 5 inches or more, 6 inches or more, 7 inches or more, 8 inches or more, 9 inches or more, 10 inches or more, 11 inches or more, 12 inches or more, 13 inches or more, 14 inches or more, 15 inches or more, 16 inches or more, 17 inches or more, 18 inches or more, 20 inches or more, 22 inches or more, 24 inches or more, 26 inches or more, 28 inches or more, 30 inches or more, 32 inches or more, or 34 inches or more). In some examples, the shredder can reduce the average initial size of the incoming plastic to 36 inches or less (longest dimension) (e.g., 34 inches or less, 32 inches or less, 30 inches or less, 28 inches or less, 26 inches or less, 24 inches or less, 22 inches or less, 20 inches or less, 18 inches or less, 17 inches or less, 16 inches or less, 15 inches or less, 14 inches or less, 13 inches or less, 12 inches or less, 11 inches or less, 10 inches or less, 9 inches or less, 8 inches or less, 7 inches or less, 6 inches or less, 5 inches or less, 4 inches or less, 3 inches or less, 2 inches or less, or 1 inch or less). The average longest dimension of the plastic processed by the shredder can range from any of the minimum values described above to any of the maximum values described above. For example, the shredder can reduce the average initial size of the incoming plastic to from 0.25 inches to 36 inches (longest dimension) (e.g., from 0.25 to 18 inches, from 18 to 36 inches, from 0.25 to 6 inches, from 6 to 12 inches, from 12 to 18 inches, from 18 to 24 inches, from 24 to 30 inches, from 30 to 36 inches, from 0.25 to 30 inches, from 0.25 to 24 inches, from 0.25 to 18 inches, from 0.25 to 16 inches, from 0.25 to 14 inches, from 0.25 to 12 inches, from 0.25 to 10 inches, from 0.25 to 8 inches, from 0.25 to 4 inches, from 0.25 to 2 inches, from 0.25 inches to 1 inch, from 1 to 36 inches, from 2 to 36 inches, from 4 to 36 inches, from 6 to 36 inches, from 8 to 36 inches, from 10 to 36 inches, from 12 to 36 inches, from 14 to 36 inches, from 16 to 36 inches, from 18 to 36 inches, from 1 to 30 inches, or from 2 to 18 inches).

(275) Plastic feedstock that passes through the shredder can then be stored in a hopper and/or transported for further processing.

(276) In some examples, the shredded feedstock can go through a second size reduction process using any suitable size reduction technique.

(277) Drying Component

(278) In some examples, the systems and methods can further include washing and/or drying the feedstock.

(279) For example, the systems and methods can further comprise drying the feedstock, for example to remove at least a portion of the moisture or other liquids comprising a contaminant within the feedstock.

(280) In some examples, the feedstock can be deposited onto a conveyor which passes the feedstock through a dryer before depositing the feedstock in a storage bunker and/or transporting the feedstock to a further system component for further processing.

(281) The dryer can comprise any suitable equipment, such as a rotary dryer. Heated air can be directed through the dryer across the feedstock to remove moisture from the feedstock. The surface area exposed can allow the heated air flow to remove moisture or free water that may be present in the feedstock. The moist air along with small, entrained particles from the dryer can be exhausted using any suitable means. The required air can be heated by any suitable means, such as electrically heated. The maximum air temperature will be below the softening point of any of the plastics. Using an effective drying solution upstream of the extruders and/or reactors can reduce the problems of vent flow at downstream extrusion equipment and water intrusion to the reactors.

(282) Storage Bunker

(283) In some examples, the system can further include a storage bunker, for example to store feedstock before undergoing melting, removal of contaminants, pyrolysis, or a combination thereof.

(284) In some examples, the system includes a storage bunker that receives the feedstock from the infeed conveyor, the shredder (when present), the dryer (when present), the trommel (when present), etc. or a combination thereof.

(285) The storage bunker can, for example, have the capacity to store enough feedstock to provide an uninterrupted supply of plastic to the downstream components (e.g., extruder(s)) for a period of time (e.g., up to two hours), for example if any of the upstream equipment has to be shut down briefly for maintenance or repair.

(286) Feedstock levels inside the storage bunker can be monitored, for example using one or more cameras or other feedback mechanisms.

(287) Metals Detection and Removal

(288) In some examples, feedstock loaded into the system can undergo additional metals detection and removal. In some examples, the plastic feedstock can be deposited onto a conveyor and/or further processed to metal contaminants. This can, for example, include visual inspection and manual removal, automated inspection and removal, positioning one or more magnets to magnetically remove ferrous contaminants (e.g., various components such as nuts, bolts, screws, small pieces of wire, etc. comprising ferrous metals and/or alloys), washing and/or drying, size based separation (e.g., screening, sifting, etc.), air jets, sink float, etc.

(289) For example, at one or more points in any of the systems or methods described herein, there can be one or more additional magnetic components to magnetically remove ferrous contaminants from the feedstock, for example before the shredder, after the shredder, before the trommel, after the trommel, before the dryer, after the dryer, before the storage bunker, after the storage bunker, before the components for melting, removal of contaminants, and/or pyrolysis, or a combination thereof. For example, the system can include magnets positioned before, after, or as part of each of the one or more conveyors that transport the feedstock between each system location/component. The strength of the magnets can be selected based on the location in the system and/or the throughput of feedstock processed.

(290) In addition, the system can further include a metal detection and rejection system to eliminate further metal contaminants, such as non-ferrous metals (e.g., copper, brass, bronze, stainless steel, aluminum and other non-ferrous alloys). Non-ferrous metals can be present in a variety of forms, such as, for example, nuts, bolts, screws, washers, batteries, machine parts, tools, etc. The additional metal detection system can be included in the system, for example, on the conveyors feeding the storage bunkers. This additional metal detection system can detect non-ferrous metals and then trigger a quick-acting diverter gate that moves this metal off the conveyor and into a collection bin. While aluminum is the primary target of this system, copper, stainless steel, and brass can also be detected and rejected.

(291) Conveyors

(292) In the system described herein, each of the conveyors can comprise any suitable type of conveyor. Examples of conveyors include, but are not limited to, belt conveyors, roller conveyors, slat conveyors, apron conveyors, ball transfer conveyors, magnetic conveyors, bucket conveyors, chute conveyors, chain conveyors, pneumatic conveyors, vacuum conveyors, screw conveyors, vibrating conveyors, wheel conveyors, sandwich conveyors, and combinations thereof. In some examples, each of the conveyors can comprise a screw conveyor, a belt conveyor, or a combination thereof. In some examples, the system can include a plurality of belt conveyors. The belt conveyors can, for example, be designed with side walls. The belt conveyors can include any type of belt conveyor, such as standard flat belts, cleated belts, semi-trough belts, compound belts (e.g., hockey stick configurations), or a combination thereof.

(293) The dimensions and/or speed of any of the conveyors can be selected in view of a variety of

factors. For example, the dimensions and/or speed of the conveyor can be selected to regulate the flow of materials at a desired rate.

(294) Melting, Removal of Contaminants, and/or Pyrolysis

(295) In some examples, the systems can include one or more components for melting the feedstock, volatilizing various contaminants in the feedstock, pyrolyzing the feedstock, or a combination thereof.

(296) While some contaminants can be physically removed by one or more of the processes discussed above, for certain feedstock components, such as multilayer films, it is difficult to physically remove the contaminants and instead they can be removed by heating the feedstock to a temperature sufficient to volatilize said contaminant.

(297) For example, the systems and methods can comprise pyrolyzing the feedstock, wherein the pyrolysis reactor and method includes a component or step for removal of volatile contaminants. The pyrolysis can be accomplished using any suitable pyrolysis reactor, such as, for example, an auger pyrolysis reactor, a rotary kiln pyrolysis reactor, a drum pyrolysis reactor, a tubular pyrolysis reactor, a fluidized bed reactor, a spouted bed reactor, a molten salt reactor, a fixed-bed reactor, a continuously stirred reactor, a Heinz Retort Pyrolysis reactor, a vortex pyrolysis reactor, a batch pyrolysis reactor, a semi-batch pyrolysis reactor, or a combination thereof.

(298) In some examples, the systems and methods can comprise heating and/or melting the feedstock before introducing the melted feedstock into a pyrolysis reactor, wherein the feedstock is heated and/or melted at a temperature sufficient to volatilize a contaminant and the systems and methods can further include removing said volatilized contaminants. Any suitable component for heating and/or melting can be used, such as those known in the art. In some examples, the systems and methods can include one or more extruders, wherein the feedstock is heated and/or melted within the extruder and optionally wherein the extruder includes one or more vents for removing volatile contaminants from the heated and/or melted feedstock.

(299) Extruders

(300) In some examples, plastic feedstock (e.g., optionally shredded plastic feedstock) from the storage bunker is conveyed separately to one or more extruders (e.g., two or more), for example using a conveyor. The extruders can be any suitable type of extruder. The extruders can, for example, be designed to heat the plastic and convert it into a semi-molten state that is moved to the reactors. In some examples, the systems includes two or more extruders and the two or more extruders can be in operation simultaneously.

(301) In some examples, the system includes a plurality of extruders and each extruder is configured to process a portion of normal throughput, for example so as to allow feedstock flow to and operation of the reactors to continue when one of the extruders is taken out of service for repair or maintenance. In some examples, the system can include three extruders, with two extruders being in operation simultaneously and the third extruder being a redundancy, for example the third extruder can be operated while one of the other extruders is taken out of service for repair or maintenance.

(302) Each extruder can, for example, use an internal pneumatically operated ram to increase the density of the plastic in order to achieve the desired throughput rate. The ram can also move the plastic from the extruder inlet into the extruder's screw mechanism.

(303) In some examples, the extruder barrel can include one or more openings (e.g. one or more vents or ports) at one or more positions along the length of the extruder barrel. In some examples, each extruder barrel can include a plurality of vents (e.g., two or more vents) along the length of the extruder barrel. The vent(s) can allow vapors and/or gases produced from the plastic feedstock during the heating process to escape from the extruder. Moisture in the feedstock is converted to steam at the high temperatures created in the extruder and this steam typically exits at the vent. Other gaseous material such as volatile inks from plastic labels, various lipids and fats from food contamination on the plastic, and decomposed PVC and PET polymers can also exit at the vent

along with gas made up of entrained fine particulates. This system allows removal of significant amounts of chlorine and other undesirable elements that otherwise would end up in the reactor and potentially affect the quality of both oil and wax products and/or corrode the processing equipment. (304) In some examples, each extruder comprises two or more vents (e.g., wherein the extruder includes at least a first vent and a second vent). In some examples, the first vent of the extruder comprises an ambient pressure vent. In some examples, the second vent of the extruder comprises a vacuum vent, for example where a vacuum is applied through the vent to pull gases and/or contaminants out of the semi-molten feedstock.

(305) In some examples, a vent feeding device can be used at one or more of the extruder vents to prevent expulsion of melted feedstock from that vent. The vent feeder can force any feedstock that is flowing or being expelled from the vent back into the barrel where it is then carried forward down the extruder. This feeder can be equipped with a vent section that can allow steam and other volatiles to pass by the feeder.

(306) In some examples, the barrel of the extruder can be heated, for example by one or more externally mounted heaters. In some examples, the barrel of the extruder can be heated by a plurality of externally mounted heaters. The heaters can be any suitable type of heater, such as resistive electric heaters and/or inductive heaters. Additional heating can, for example, be provided by friction as the feedstock is forced through the internal geometry of the extruder barrel by the screw. Multiple zones along the length of the extruder can, in some examples, be independently heated and cooled using barrel heaters and/or cooling fans to achieve a pre-set temperature profile that varies depending on the type of material being fed into the extruder.

(307) In some examples, the barrel of the extruder can be heated such that the feedstock within the extruder has a temperature of 20° C. or more at the first of the one or more vents (e.g., 25° C. or more, 50° C. or more, 75° C. or more, 100° C. or more, 125° C. or more, 150° C. or more, 175° C. or more, 200° C. or more, 225° C. or more, 250° C. or more, 275° C. or more, 280° C. or more, 285° C. or more, 290° C. or more, 295° C. or more, 300° C. or more, 305° C. or more, 310° C. or more, 315° C. or more, 320° C. or more, 325° C. or more, 350° C. or more, 375° C. or more, 400° C. or more, or 425° C. or more). In some examples, the barrel of the extruder can be heated such that the feedstock within the extruder has a temperature of 450° C. or less at the first of the one or more vents (e.g., 425° C. or less, 400° C. or less, 375° C. or less, 350° C. or less, 325° C. or less, 320° C. or less, 315° C. or less, 310° C. or less, 305° C. or less, 300° C. or less, 295° C. or less, 290° C. or less, 285° C. or less, 280° C. or less, 275° C. or less, 250° C. or less, 225° C. or less, 200° C. or less, 175° C. or less, 150° C. or less, 125° C. or less, 100° C. or less, 75° C. or less, or 50° C. or less). The temperature of the feedstock within the extruder at the first vent can range from any of the minimum values described above to any of the maximum values described above. For example, the barrel of the extruder can be heated such that the feedstock within the extruder has a temperature of from 20° C. to 450° C. at the first of the one or more vents (e.g., from 20° C. to 225° C., from 225° C. to 450° C., from 20° C. to 125° C., from 125° C. to 225° C., from 225° C. to 325° C., from 325° C. to 450° C., from 20° C. to 400° C., from 20° C. to 350° C., from 20° C. to 300° C., from 20° C. to 250° C., from 20° C. to 200° C., from 20° C. to 250° C., from 20° C. to 100° C., from 20° C. to 50° C., from 50° C. to 450° C., from 100° C. to 450° C., from 150° C. to 450° C., from 200° C. to 250° C., from 250° C. to 250° C., from 300° C. to 450° C., from 350° C. to 450° C., from 50° C. to 400° C., from 100° C. to 375° C., from 250° C. to 350° C., or from 275° C. to 325° C.).

(308) In some examples, each extruder includes a screw with multiple zones, such as a pumping section, a compression section, a decompression section, a mixing section, or a combination thereof. In some examples, each extruder screw includes a decompression section at or before the first vent, for example to promote expulsion of entrained air, moisture, and/or other gases (e.g., volatiles) from the feedstock at the first vent.

(309) The residence time of the feedstock within each extruder can be selected in view of a variety

of factors. For example, the residence time of the feedstock within each extruder can be selected in view of the speed at which the extruder is run (which in turn can be selected based on the throughput rate of the reactor(s) that the extruder is feeding), the identity of the plastics within the feedstock, or a combination thereof.

(310) In some examples, the residence time of the feedstock within the extruder can be 30 seconds or more (e.g., 1 minute or more, 1.5 minutes or more, 2 minutes or more, 2.5 minutes or more, 3 minutes or more, 3.5 minutes or more, 4 minutes or more, 5 minutes or more, 5.5 minutes or more, 6 minutes or more, 6.5 minutes or more, 7 minutes or more, 7.5 minutes or more, 8 minutes or more, 8.5 minutes or more, or 9 minutes or more). In some examples, the residence time of the feedstock within the extruder can be 10 minutes or less (e.g., 9.5 minutes or less, 9 minutes or less, 8.5 minutes or less, 8 minutes or less, 7.5 minutes or less, 7 minutes or less, 6.5 minutes or less, 6 minutes or less, 5.5 minutes or less, 5 minutes or less, 4.5 minutes or less, 4 minutes or less, 3.5 minutes or less, 3 minutes or less, 2.5 minutes or less, 2 minutes or less, 1.5 minutes or less, or 1 minute or less). The residence time of the feedstock within the extruder can range from any of the minimum values described above to any of the maximum values described above. For example, the residence time of the feedstock within the extruder can be from 30 seconds to 10 minutes (e.g., from 30 seconds to 5 minutes, from 5 minutes to 10 minutes, from 30 seconds to 2.5 minutes, from 2.5 to 5 minutes, from 5 to 7.5 minutes, from 7.5 minutes to 10 minutes, from 30 seconds to 9 minutes, from 30 seconds to 8 minutes, from 30 seconds to 7 minutes, from 30 seconds to 6 minutes, from 30 seconds to 4 minutes, from 30 seconds to 3 minutes, from 30 seconds to 2 minutes, from 1 minute to 10 minutes, from 2 to 10 minutes, from 3 to 10 minutes, from 4 to 10 minutes, from 6 to 10 minutes, from 7 to 10 minutes, from 8 to 10 minutes, from 1 minute to 9 minutes, or from 1.5 minutes to 5 minutes).

(311) Feedstock material subsequently enters the extruder screw's pumping section where it is propelled out of the extruder and into the pyrolysis reactor, for example via a heated transfer pipe. A rupture disk can be provided for emergency pressure relief to prevent down-stream damage to piping and equipment.

(312) FIG. 24 provides a perspective view of an example implementation of an extruder **100** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. The molten or semi-molten state output by the extruder **100** may be directed to a pyrolysis reactor for depolymerization (e.g., various implementations of the pyrolysis reactors discussed herein). FIG. 25 shows a cross-sectional view of the extruder **100** shown in FIG. 24. Certain elements depicted in FIG. 24 are also depicted in FIG. 25 and, accordingly, reference to either figure may be regarded as a reference to both figures.

(313) As shown in FIG. 24, the extruder **100** includes a motor **102** (e.g., three-phase AC motor) configured to drive a screw **142** within an extruder barrel **110**. The motor **102** is coupled to a reducer assembly **104** and cooling system **106**. The cooling system **106** is configured to maintain desired temperatures within the reducer assembly and or motor. The extruder screw **142** is coupled to a drive shaft via a seal assembly **108**, allowing the motor **302** to drive rotation of the extruder screw **142**.

(314) Plastic feedstock is directed into the extruder barrel **110** via a hopper **120**, which is configured to receive plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). A pneumatic ram **122** is configured to increase the density of the plastic feedstock in order to assist in achieving a desired throughput rate within the extruder **100**.

(315) The extruder **100** includes a single extruder screw **142** housed within a heated barrel **110**. As shown in FIG. 24, the barrel **110** can be encased by heating elements **144** configured for heating

various zones along the length of the extruder barrel **110**. In one implementation, the heating elements **144** can comprise electric heaters. In other implementations, the heating elements **144** can comprise forced-air, gas, indirect, or direct heating arrangements. In various implementations, the extruder **100** may include multiple heating elements **144** disposed throughout the length of the extruder **100** configured to heat the extruder barrel **110**. For example, in one implementation, the extruder **300** includes between two and fifteen electric heaters defining between two and fifteen heating zones along the length of the barrel **110**. The heaters (e.g., electric heaters) can be controlled to obtain a desired temperature gradient along the length of the extruder barrel **110**, such that the temperature of the feedstock within the extruder barrel **110** reaches desired temperatures. Additional heating is provided by friction as the plastic is forced through the internal geometry of the extruder barrel by the screw. In other implementations, two extruder screws may be used within the barrel **110**.

(316) In various implementations, the extruder screw **142** within the barrel **110** is provided with multiple zones (e.g., a pumping section, a compression section, and a decompression section). In the pumping section, the molten (or semi-molten) feedstock material is propelled out of the extruder (e.g., via a barrel outlet **140** shown in FIG. **24**) and into the pyrolysis reactor (e.g., via a heated transfer pipe).

(317) FIG. **26** provides a perspective view of another example implementation of an extruder **200** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **200**'s barrel is labeled **210**). FIG. **27** shows a cross-sectional view of the extruder **200** shown in FIG. **26**. Certain elements depicted in FIG. **26** are also depicted in FIG. **27** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(318) In the illustrated embodiment, the extruder **200** is configured as a twin screw extruder. As shown in FIGS. **26** and **27**, a pair of extruder screws **242**, **243** are provided in the extruder's barrel **210**. In various implementations, the screws are configured for **242**, **243** are configured for driving the feedstock material through the barrel **210** as the feedstock material is heated.

(319) FIG. **28** provides a perspective view of another example implementation of an extruder **300** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **300**'s barrel is labeled **310**).

(320) In the illustrated embodiment, the extruder **300** includes one or more gas powered heating elements **346**. As shown in FIG. **28**, the gas-powered heating elements **346** are configured for heating the extruder's barrel **310** in order to thereby heat the feedstock material being translated through the barrel **310**. Although the extruder **300** is depicted with a single screw **342**, in other implementations, the extruder **300** may be provided with twin screws. Additionally, various implementations may include a combination of gas and electric heating elements for heating the barrel **310**.

(321) FIG. **29** provides a perspective view of another example implementation of an extruder **400** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **400**'s barrel is labeled **410**).

(322) In the illustrated embodiment, the extruder **400** includes one or more oil-based heating

elements **346**. As shown in FIG. **28**, the oil-based heating elements **445** may define a series of conduits or channels around the barrel **410**, through which heated oil (or another suitable liquid) may be pumped. In this way, the oil-based heating elements **445** are configured for heating the extruder's barrel **410** in order to thereby heat the feedstock material being translated through the barrel **410**. In various implementations, the heated oil may be heated by electric or gas-powered heating elements associated with the oil-based heating elements **445**. Although the extruder **400** is depicted with a single screw **442**, in other implementations, the extruder **400** may be provided with twin screws. Additionally, various implementations may include a combination of oil, gas, and electric heating elements for heating the barrel **410**.

(323) FIG. **30** provides a perspective view of another example implementation of an extruder **500** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **500**'s barrel is labeled **510**).

(324) As shown in FIG. **30**, electric heaters **544** are positioned around the extruder's barrel **510**. In addition, a vent **532**. Generally, the vent **532** is configured to allow vapors and/or gases produced from the plastic feedstock during the heating process to escape from the extruder **500**. In this way, the vent **532** may allow for removal of residual vapor and contaminants that can have a negative impact on the oil, wax, or gas product quality. In one implementation, the vent **532** is an ambient pressure vent. In other implementations, the vent **532** is under vacuum.

(325) Although the extruder **500** is depicted with a single screw **542**, in other implementations, the extruder **500** may be provided with twin screws. Additionally, various implementations may include a combination of oil, gas, and electric heating elements for heating the barrel **510**.

(326) FIG. **31** provides a perspective view of another example implementation of an extruder **600** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **600**'s barrel is labeled **610**).

(327) As shown in FIG. **31**, electric heaters **644** are positioned around the extruder's barrel **610**. In addition, a pair of vents **632**, **634** are provided along the extruder's barrel **610**. Generally, the vents **632**, **634** are configured to allow vapors and/or gases produced from the plastic feedstock during the heating process to escape from the extruder **600**. In this way, the vents **632**, **634** may allow for removal of residual vapor and contaminants that can have a negative impact on the oil, wax, or gas product quality. In one implementation, both vents **632**, **634** are ambient pressure vents. In other implementations, both vents **632**, **634** are under vacuum. In other implementations, the first vent **632** is an ambient pressure vent while the second vent **634** is under vacuum.

(328) Although the extruder **600** is depicted with a single screw **642**, in other implementations, the extruder **600** may be provided with twin screws. Additionally, various implementations may include a combination of oil, gas, and electric heating elements for heating the barrel **610**.

(329) FIG. **32** provides a perspective view of another example implementation of an extruder **700** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **700**'s barrel is labeled **710**).

(330) As shown in FIG. **32**, electric heaters **744** are positioned around the extruder's barrel **710**. In addition, four vents **732**, **734**, **736**, **738** are provided along the extruder's barrel **710**. Generally, the vents **732**, **734**, **736**, **738** are configured to allow vapors and/or gases produced from the plastic

feedstock during the heating process to escape from the extruder **700**. In this way, the vents **732, 734, 736, 738** may allow for removal of residual vapor and contaminants that can have a negative impact on the oil, wax, or gas product quality. In one implementation, the vents **732, 734, 736, 738** are ambient pressure vents. In other implementations, the vents **732, 734, 736, 738** are under vacuum. In other implementations, one or more of the vents **732, 734, 736, 738** are ambient pressure vents while one or more of the vents **732, 734, 736, 738** are under vacuum.

(331) Although the extruder **700** is depicted with a single screw **742**, in other implementations, the extruder **700** may be provided with twin screws. Additionally, various implementations may include a combination of oil, gas, and electric heating elements for heating the barrel **710**.

(332) FIG. **33** provides a perspective view of another example implementation of an extruder **800** configured for heating plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics) and converting the feedstock into a molten or semi-molten state. Elements shared with the extruder **100** are given common references (e.g., the extruder **100**'s barrel is labeled **110** while the extruder **800**'s barrel is labeled **810**).

(333) As shown in FIG. **33**, electric heaters **844** are positioned around the extruder's barrel **810**. In addition, a pair of vents **832, 834** are provided along the extruder's barrel **810**. Generally, the vents **832, 834** are configured to allow vapors and/or gases produced from the plastic feedstock during the heating process to escape from the extruder **800**. In this way, the vents **832, 834** may allow for removal of residual vapor and contaminants that can have a negative impact on the oil, wax, or gas product quality. In one implementation, both vents **832, 834** are ambient pressure vents. In other implementations, both vents **832, 834** are under vacuum. In other implementations, the first vent **832** is an ambient pressure vent while the second vent **834** is under vacuum.

(334) Although the extruder **800** is depicted with a single screw **842**, in other implementations, the extruder **800** may be provided with twin screws. Additionally, various implementations may include a combination of oil, gas, and electric heating elements for heating the barrel **810**.

(335) In the illustrated implementation, a vent feeding device **900** is used at the first vent **832** to prevent expulsion of melted plastic from the vent **832**. As an example, FIG. **34** shows a vent feeding device **900** according to one implementation. As shown in FIG. **34**, the vent feeding device **900** is elevated on a stand **902** with wheels **940** and configured to be selectively engaged with the vent **832** via a vent inlet interface **922**. The vent feeding device **900** further includes a motor **904** that is coupled to a gearbox **906** and configured for driving single or twin screw elements (not shown) disposed within a vent inlet **920**. The vent feeder **900** also includes a vapor outlet **930** (e.g., a vent) that will allow vapor and contaminants to pass by the screw(s) (e.g., into a scrubber system). In addition to removing contaminants, the vent feeding device **900** serves to prevent the occurrence of an event flow from the extruder (e.g., preventing molten feedstock from being expelled from the extruder vent **832**).

(336) Pyrolysis Reactors

(337) The hydrocarbons that make up the feedstock plastic polymers include chains and rings of hydrocarbon molecules linked together to form the solid materials with some additives to the structures to adjust properties such as plasticity, stabilization against ultraviolet light degradation, and extrusion slip.

(338) Oil and wax production is accomplished by heating the incoming stream of plastic (e.g., raw feedstock, melted feedstock, semi-molten feedstock from the extruders, etc.) in an oxygen-free environment to the point where the plastic is a fully molten liquid and the polymers “depolymerize”. During the conversion process, the hydrocarbon plastic chains and groups of rings are split apart by the heating process into smaller segments until they are small and light enough to exit the reactor as a vapor.

(339) For example, the systems and methods can include one or more pyrolysis reactors (e.g., two or more, or three or more) for pyrolyzing the feedstock. The pyrolysis can be accomplished using

any suitable pyrolysis reactor, such as, for example, an auger pyrolysis reactor, a rotary kiln pyrolysis reactor, a drum pyrolysis reactor, a tubular pyrolysis reactor, a fluidized bed reactor, a spouted bed reactor, a molten salt reactor, a molten metal reactor, a fixed-bed reactor, a continuously stirred reactor, a Heinz Retort Pyrolysis reactor, a vortex pyrolysis reactor, a batch pyrolysis reactor, a semi-batch pyrolysis reactor, or a combination thereof. In some examples, the system and methods can include one or more batch pyrolysis reactors, semi-batch pyrolysis reactors, a continuously stirred reactor, or a combination thereof. The reactors can have any suitable orientation, such as horizontal or vertical. In some examples, the reactors are vertical reactors.

(340) Each reactor can receive feedstock from one or more upstream components (e.g., storage bunker, extruder, etc.).

(341) In some examples, the system includes one or more reactors (e.g., two or more, or three or more) configured to receive the semi-molten feedstock from the extruder(s). In some examples, the system can include a plurality of reactors. Each reactor can, for example, process the output of one or more extruders.

(342) The volume of each reactor can be selected, for example, in view of the throughput of the system.

(343) In some examples, the volume of each reactor can independently be 1 cubic foot (ft.³) or more (e.g., 2 ft.³ or more, 3 ft.³ or more, 4 ft.³ or more, 5 ft.³ or more, 10 ft.³ or more, 15 ft.³ or more, 20 ft.³ or more, 25 ft.³ or more, 30 ft.³ or more, 35 ft.³ or more, 40 ft.³ or more, 45 ft.³ or more, 50 ft.³ or more, 60 ft.³ or more, 70 ft.³ or more, 80 ft.³ or more, 90 ft.³ or more, 100 ft.³ or more, 125 ft.³ or more, 150 ft.³ or more, 175 ft.³ or more, 200 ft.³ or more, 225 ft.³ or more, 250 ft.³ or more, 300 ft.³ or more, 350 ft.³ or more, 400 ft.³ or more, 450 ft.³ or more, 500 ft.³ or more, 600 ft.³ or more, 700 ft.³ or more, 800 ft.³ or more, 900 ft.³ or more, 1,000 ft.³ or more, 1,100 ft.³ or more, 1,200 ft.³ or more, 1,300 ft.³ or more, or 1,400 ft.³ or more). In some examples, the volume of each reactor can independently be 1,500 ft.³ or less (e.g., 1,400 ft.³ or less, 1,300 ft.³ or less, 1,200 ft.³ or less, 1,100 ft.³ or less, 1,000 ft.³ or less, 900 ft.³ or less, 800 ft.³ or less, 700 ft.³ or less, 600 ft.³ or less, 500 ft.³ or less, 450 ft.³ or less, 400 ft.³ or less, 350 ft.³ or less, 300 ft.³ or less, 250 ft.³ or less, 225 ft.³ or less, 200 ft.³ or less, 175 ft.³ or less, 150 ft.³ or less, 125 ft.³ or less, 100 ft.³ or less, 90 ft.³ or less, 80 ft.³ or less, 70 ft.³ or less, 60 ft.³ or less, 50 ft.³ or less, 45 ft.³ or less, 40 ft.³ or less, 35 ft.³ or less, 30 ft.³ or less, 25 ft.³ or less, 20 ft.³ or less, 15 ft.³ or less, 10 ft.³ or less, 5 ft.³ or less, 4 ft.³ or less, 3 ft.³ or less, or 2 ft.³ or less). The volume of each reactor can independently range from any of the minimum values described above to any of the maximum values described above. For example, the volume of each reactor can independently be from 1 ft.³ to 1,500 ft.³ (e.g., from 1 to 750 ft.³, from 750 to 1,500 ft.³, from 1 to 500 ft.³, from 500 to 1,000 ft.³, from 1,000 to 1,500 ft.³, from 1 to 1,400 ft.³, from 1 to 1,300 ft.³, from 1 to 1,200 ft.³, from 1 to 1,100 ft.³, from 1 to 1,000 ft.³, from 1 to 900 ft.³, from 1 to 800 ft.³, from 1 to 700 ft.³, from 1 to 600 ft.³, from 1 to 400 ft.³, from 1 to 300 ft.³, from 1 to 200 ft.³, from 1 to 100 ft.³, from 1 to 50 ft.³, from 1 to 25 ft.³, from 1 to 10 ft.³, from 10 to 1,500 ft.³, from 25 to 1,500 ft.³, from 50 to 1,500 ft.³, from 100 to 1,500 ft.³, from 200 to 1,500 ft.³, from 300 to 1,500 ft.³, from 400 to 1,500 ft.³, from 500 to 1,500 ft.³, from 600 to 1,500 ft.³, from 700 to 1,500 ft.³, from 800 to 1,500 ft.³, from 900 to 1,500 ft.³, from 1,200 to 1,500 ft.³, from 1,300 to 1,500 ft.³, from 10 to 1,400 ft.³, from 100 to 1,000 ft.³, or from 500 to 750 ft.³).

(344) In some examples, the volume of each reactor can independently be 100 gallons or more (e.g., 250 gallons or more, 500 gallons or more, 750 gallons or more, 1,000 gallons or more, 1,500

gallons or more, 2,000 gallons or more, 2,500 gallons or more, 3,000 gallons or more, 3,500 gallons or more, 4,000 gallons or more, 4,500 gallons or more, 5,000 gallons or more, 5,500 gallons or more, 6,000 gallons or more, 6,500 gallons or more, 7,000 gallons or more, 7,500 gallons or more, 8,000 gallons or more, 8,500 gallons or more, or 9,000 gallons or more). In some examples, the volume of each reactor can independently be 20,000 gallons or less (e.g., 9,500 gallons or less, 9,000 gallons or less, 8,500 gallons or less, 8,000 gallons or less, 7,500 gallons or less, 7,000 gallons or less, 6,500 gallons or less, 6,000 gallons or less, 5,500 gallons or less, 5,000 gallons or less, 4,500 gallons or less, 4,000 gallons or less, 3,500 gallons or less, 3,000 gallons or less, 2,500 gallons or less, 2,000 gallons or less, 1,500 gallons or less, 1,000 gallons or less, 750 gallons or less, 500 gallons or less, or 250 gallons or less). The volume of each reactor can independently range from any of the minimum values described above to any of the maximum values described above. For example, the volume of each reactor can independently be from 100 gallons to 20,000 gallons (e.g., from 100 to 1,000 gallons, from 1,000 to 20,000 gallons, from 100 to 500 gallons, from 500 to 1,000 gallons, from 1,000 to 5,000 gallons, from 5,000 to 20,000 gallons, from 100 to 9,000 gallons, from 100 to 8,000 gallons, from 100 to 8,000 gallons, from 100 to 7,000 gallons, from 100 to 6,000 gallons, from 100 to 5,000 gallons, from 100 to 4,000 gallons, from 100 to 3,000 gallons, from 100 to 2,000 gallons, from 500 to 20,000 gallons, from 1,000 to 10,000 gallons, from 2,000 to 20,000 gallons, from 3,000 to 20,000 gallons, from 4,000 to 20,000 gallons, from 6,000 to 20,000 gallons, from 7,000 to 20,000 gallons, from 8,000 to 20,000 gallons, from 500 to 9,000 gallons, or from 1,000 to 7,500 gallons).

(345) Each reactor is equipped with heaters, for example internal and/or external heaters. The heaters can be any suitable type of heaters, such as electric, microwave, and/or gas heaters. The heaters provide the heat needed to raise temperatures inside the reactor to a point where the depolymerization process takes place. In some examples, a plurality of heaters can be arrayed on the reactor's exterior and/or within its interior.

(346) In some examples, the heaters are gas heaters (e.g., gas powered heaters), which can be fed from commercial gas fuel and/or recycled hydrocarbon gases recovered from the reactor products (e.g., propane, butane, and/or pentane). In some examples, the heaters are electric heaters (e.g., electrically powered heaters, resistive heaters, inductive heaters, etc.). In some examples, the electric heaters can be powered by a generator, which in turn can be gas powered and which can be fed from commercial gas fuel and/or recycled hydrocarbon gases recovered from the reactor products (e.g., propane, butane, and/or pentane).

(347) In some examples, the reactors are equipped with a plurality of internal electric heaters, e.g. a plurality of electric heaters disposed within the reactor (e.g., 2 or more, 3 or more, 4 or more, 5 or more, 6 or more, 7 or more, 8 or more, 9 or more, 10 or more, 11 or more, 12 or more, 13 or more, 14 or more, or 15 or more). The electric heaters can, for example, be oriented in any suitable direction (e.g., horizontally, vertically, angled) within each reactor inside dry wells. The electric heater temperature can be controlled to provide a prescribed temperature and heat density to the dry well walls which in turn provide a controlled heat flux into the feedstock bath to drive the reactions and minimizing char formation. The number of internal heaters can, for example, be selected based on the size of the reactor and/or the size of the heaters. Supplemental electric heaters on the outer surface of the reactors can also be provided that operate at the same temperatures and heat density as the internal heaters, as necessary.

(348) The heat density applied by each of the internal and/or external heaters can, for example, independently be 5 watts per square inch (W/in.^{sup.2}) or more (e.g., 6 W/in.^{sup.2} or more, 7 W/in.^{sup.2} or more, 8 W/in.^{sup.2} or more, 9 W/in.^{sup.2} or more, 10 W/in.^{sup.2} or more, 11 W/in.^{sup.2} or more, 12 W/in.^{sup.2} or more, 13 W/in.^{sup.2} or more, 14 W/in.^{sup.2} or more, 15 W/in.^{sup.2} or more, 16 W/in.^{sup.2} or more, 17 W/in.^{sup.2} or more, 18 W/in.^{sup.2} or more, 19 W/in.^{sup.2} or more, 20 W/in.^{sup.2} or more, 21 W/in.^{sup.2} or more, 22 W/in.^{sup.2} or more, 23 W/in.^{sup.2} or more, 24 W/in.^{sup.2} or more, 25 W/in.^{sup.2} or more, 26 W/in.^{sup.2} or more, 27

W/in.sup.2 or more, 28 W/in.sup.2 or more, 29 W/in.sup.2 or more, 30 W/in.sup.2 or more, 31 W/in.sup.2 or more, 32 W/in.sup.2 or more, 33 W/in.sup.2 or more, 34 W/in.sup.2 or more, 35 W/in.sup.2 or more, 36 W/in.sup.2 or more, 37 W/in.sup.2 or more, 38 W/in.sup.2 or more, 39 W/in.sup.2 or more, 40 W/in.sup.2 or more, 41 W/in.sup.2 or more, 42 W/in.sup.2 or more, or 43 W/in.sup.2 or more, 44 W/in.sup.2 or more, 45 W/in.sup.2 or more, 46 W/in.sup.2 or more, 47 W/in.sup.2 or more, 48 W/in.sup.2 or more, 49 W/in.sup.2 or more, 50 W/in.sup.2 or more, 51 W/in.sup.2 or more, 52 W/in.sup.2 or more, 53 W/in.sup.2 or more, 54 W/in.sup.2 or more). In some examples, the heat density applied by each of the internal and/or external heaters can independently be 55 W/in.sup.2 or less (e.g., 55 W/in.sup.2 or less, 54 W/in.sup.2 or less, 53 W/in.sup.2 or less, 52 W/in.sup.2 or less, 51 W/in.sup.2 or less, 50 W/in.sup.2 or less, 49 W/in.sup.2 or less, 48 W/in.sup.2 or less, 47 W/in.sup.2 or less, 46 W/in.sup.2 or less, 45 W/in.sup.2 or less, 44 W/in.sup.2 or less, 43 W/in.sup.2 or less, 42 W/in.sup.2 or less, 41 W/in.sup.2 or less, 40 W/in.sup.2 or less, 39 W/in.sup.2 or less, 38 W/in.sup.2 or less, 37 W/in.sup.2 or less, 36 W/in.sup.2 or less, 35 W/in.sup.2 or less, 34 W/in.sup.2 or less, 33 W/in.sup.2 or less, 32 W/in.sup.2 or less, 31 W/in.sup.2 or less, 30 W/in.sup.2 or less, 29 W/in.sup.2 or less, 28 W/in.sup.2 or less, 27 W/in.sup.2 or less, 26 W/in.sup.2 or less, 25 W/in.sup.2 or less, 24 W/in.sup.2 or less, 23 W/in.sup.2 or less, 22 W/in.sup.2 or less, 21 W/in.sup.2 or less, 20 W/in.sup.2 or less, 19 W/in.sup.2 or less, 18 W/in.sup.2 or less, 17 W/in.sup.2 or less, 16 W/in.sup.2 or less, 15 W/in.sup.2 or less, 14 W/in.sup.2 or less, 13 W/in.sup.2 or less, 12 W/in.sup.2 or less, 11 W/in.sup.2 or less, 10 W/in.sup.2 or less, 9 W/in.sup.2 or less, 8 W/in.sup.2 or less, or 7 W/in.sup.2 or less). The heat density applied by each of the internal and/or external heaters can independently range from any of the minimum values described above to any of the maximum values described above. For example, the heat density applied by each of the internal and/or external heaters can independently be from 5 to 55 W/in.sup.2 (e.g., from 5 to 25 W/in.sup.2, from 25 to 55 W/in.sup.2, from 5 to 15 W/in.sup.2, from 15 to 25 W/in.sup.2, from 25 to 35 W/in.sup.2, from 35 to 55 W/in.sup.2, from 5 to 40 W/in.sup.2, from 5 to 35 W/in.sup.2, from 5 to 30 W/in.sup.2, from 5 to 20 W/in.sup.2, from 10 to 55 W/in.sup.2, from 15 to 55 W/in.sup.2, from 20 to 55 W/in.sup.2, from 30 to 55 W/in.sup.2, from 10 to 40 W/in.sup.2, from 15 to 35 W/in.sup.2, from 12 to 30 W/in.sup.2, or from 16 to 24 W/in.sup.2).

(349) The combined energy density applied by the reactor's internal and/or external heater systems can, for example, independently be 0.05 kilowatts per pound of pyrolyzed product produced within the reactor (kW/lb.) or more (e.g., 0.05 kW/lb. or more, 0.10 kW/lb. or more, 0.15 kW/lb. or more, 0.20 kW/lb. or more, 0.25 kW/lb. or more, 0.30 kW/lb. or more, 0.35 kW/lb. or more, 0.40 kW/lb. or more, 0.45 kW/lb. or more, 0.50 kW/lb. or more, 0.55 kW/lb. or more, 0.60 kW/lb. or more, 0.65 kW/lb. or more, 0.70 kW/lb. or more, 0.75 kW/lb. or more, 0.80 kW/lb. or more, 0.85 kW/lb. or more, 0.90 kW/lb. or more, 0.95 kW/lb. or more). In some examples, the combined energy density applied by the reactor's internal and/or external heater systems can, for example, independently be 1.0 kW/lb. or less (e.g., 0.95 kW/lb. or less, 0.90 kW/lb. or less, 0.85 kW/lb. or less, 0.80 kW/lb. or less, 0.75 kW/lb. or less, 0.70 kW/lb. or less, 0.65 kW/lb. or less, 0.60 kW/lb. or less, 0.55 kW/lb. or less, 0.50 kW/lb. or less, 0.45 kW/lb. or less, 0.40 kW/lb. or less, 0.35 kW/lb. or less, 0.30 kW/lb. or less, 0.25 kW/lb. or less, 0.20 kW/lb. or less, 0.15 kW/lb. or less, 0.10 kW/lb. or less). The combined energy density applied by the reactor's internal and/or external heater systems can, for example, independently range from any of the minimum values described above to any of the maximum values described above. For example, the combined energy density applied by the reactor's internal and/or external heater systems can independently be from 0.05 to 1.0 kW/lb. (e.g., from 0.05 to 0.25 kW/lb., from 0.25 to 0.50 kW/lb., from 0.50 to 0.75 kW/lb., from 0.75 to 1.0 kW/lb., from 0.05 to 0.15 kW/lb., from 0.15 to 0.30 kW/lb., from 0.30 to 0.45 kW/lb., from 0.45 to 0.60 kW/lb., from 0.60 to 0.75 kW/lb., from 0.75 to 0.90 kW/lb., or from 0.90 to 1.0 kW/lb.).

(350) The depolymerization process can produce light hydrocarbon gases (e.g., propane, butane,

and/or pentane) which can be separated from the oil and wax product streams and used as an energy source, fuel, or chemical feedstock.

(351) Localized overheating and/or high temperatures can result in solid char (coke) formation. Char buildup can require periodic clean out of a reactor for char removal from heating surfaces. Loose char can also be formed by any wood, cardboard, or paper materials that enter the system as part of the feedstock. Reactor temperature monitoring, accurate and precise individual heater control, and good heat transfer from the heaters into the liquid feedstock can, for example, be selected to control and limit the amount and/or rate of char formation.

(352) The feedstock can, for example, be heated to a temperature of 200° C. or more within the reactor (e.g., 225° C. or more, 250° C. or more, 275° C. or more, 300° C. or more, 325° C. or more, 350° C. or more, 375° C. or more, 400° C. or more, 425° C. or more, 450° C. or more, 475° C. or more, 500° C. or more, 550° C. or more, 600° C. or more, 650° C. or more, 700° C. or more, or 750° C. or more). In some examples, the feedstock can be heated to a temperature of 800° C. or less within the reactor (e.g., 750° C. or less, 700° C. or less, 650° C. or less, 600° C. or less, 550° C. or less, 500° C. or less, 475° C. or less, 450° C. or less, 425° C. or less, 400° C. or less, 375° C. or less, 350° C. or less, 325° C. or less, 300° C. or less, 275° C. or less, or 250° C. or less). The temperature to which the feedstock is heated within the reactor can range from any of the minimum values described above to any of the maximum values described above. For example, the feedstock can be heated to a temperature of from 200° C. to 800° C. within the reactor (e.g., from 200° C. to 500° C., from 500° C. to 800° C., from 200° C. to 300° C., from 300° C. to 400° C., from 400° C. to 500° C., from 500° C. to 600° C., from 600° C. to 700° C., from 700° C. to 800° C., from 200° C. to 700° C., from 200° C. to 600° C., from 200° C. to 400° C., from 300° C. to 800° C., from 400° C. to 800° C., from 600° C. to 800° C., from 250° C. to 750° C., from 300° C. to 700° C., from 350° C. to 500° C., from 375° C. to 425° C., or from 385° C. to 415° C.).

(353) The liquid and/or vapor phase feedstock inside a reactor can be agitated. For example, the pyrolysis reactor can comprise an auger pyrolysis reactor, a rotary kiln pyrolysis reactor, a fluidized bed reactor, a continuously stirred reactor, or a combination thereof, wherein the reactor agitates the liquid and/or vapor phase feedstock.

(354) In some examples, the liquid and/or vapor phase feedstock inside a reactor can be kept in continuous motion using an agitator that circulates the liquid and/or vapor phase feedstock inside the reactor. For example, the liquid feedstock can be agitated in a manner that fosters heat transfer from the internal and/or external heaters to the liquid. Liquid feedstock is a good insulator (i.e., has a low thermal conductivity) and the ability to get heat into it in a way that does not lead to charring but still provides enough heat to promote depolymerization can be an important factor.

(355) For example, each reactor can include an agitator, for example a mixer or stirrer comprising one or more blades. The agitator can be configured so that it can produce liquid flow velocities inside the reactor such that the bath acquires the necessary heat and also avoids long residence times at the heated surfaces. For example, the agitator can be configured such that the entire liquid bath is agitated, e.g. substantially none of the liquid bath is static.

(356) The agitator can, for example, be operated at a speed of 20 RPM or more (e.g., 25 RPM or more, 30 RPM or more, 35 RPM or more, 40 RPM or more, 45 RPM or more, 50 RPM or more, 55 RPM or more, 60 RPM or more, 65 RPM or more, 70 RPM or more, 75 RPM or more, 80 RPM or more, 85 RPM or more, 90 RPM or more, 95 RPM or more, 100 RPM or more, 105 RPM or more, 110 RPM or more, 115 RPM or more, 120 RPM or more, 125 RPM or more, 130 RPM or more, 135 RPM or more, 140 RPM or more, 145 RPM or more, 150 RPM or more, 155 RPM or more, 160 RPM or more, 165 RPM or more, 170 RPM or more, 175 RPM or more, 180 RPM or more, 185 RPM or more, or 190 RPM or more). In some examples, the agitator can be operated at a speed of 200 RPM or less (e.g., 195 RPM or less, 190 RPM or less, 185 RPM or less, 180 RPM or less, 175 RPM or less, 170 RPM or less, 165 RPM or less, 160 RPM or less, 155 RPM or less, 150 RPM or less, 145 RPM or less, 140 RPM or less, 135 RPM or less, 130 RPM or less, 125 RPM or less,

120 RPM or less, 115 RPM or less, 110 RPM or less, 105 RPM or less, 100 RPM or less, 95 RPM or less, 90 RPM or less, 85 RPM or less, 80 RPM or less, 75 RPM or less, 70 RPM or less, 65 RPM or less, 60 RPM or less, 55 RPM or less, 50 RPM or less, 45 RPM or less, 40 RPM or less, 35 RPM or less, or 30 RPM or less). The speed at which the agitator is operated can range from any of the minimum values described above to any of the maximum values described above. For example, the agitator can be operated at a speed of from 20 to 200 RPM (e.g., from 20 to 125 RPM, from 125 to 200 RPM, from 20 to 60 RPM, from 60 to 100 RPM, from 100 RPM to 140 RPM, from 140 to 200 RPM, from 20 to 180 RPM, from 20 to 160 RPM, from 20 to 140 RPM, from 20 to 120 RPM, from 20 to 100 RPM, from 20 to 80 RPM, from 20 to 40 RPM, from 40 to 200 RPM, from 60 to 200 RPM, from 80 to 200 RPM, from 100 to 200 RPM, from 120 to 200 RPM, from 140 to 200 RPM, from 160 to 200 RPM, from 25 to 195 RPM, from 30 to 190 RPM, from 50 to 175 RPM, from 75 to 150 RPM, or from 120 to 160 RPM).

(357) The agitator can be configured to produce homogeneous or inhomogeneous fluid (e.g., liquid and/or vapor) flow inside the reactor. In some examples, the agitator is configured to produce average fluid flow velocities inside the reactor of greater than 0 meters per second (m/s) (e.g., 0.05 m/s or more, 0.1 m/s or more, 0.15 m/s or more, 0.2 m/s or more, 0.25 m/s or more, 0.3 m/s or more, 0.35 m/s or more, 0.4 m/s or more, 0.45 m/s or more, 0.5 m/s or more, 0.6 m/s or more, 0.7 m/s or more, 0.8 m/s or more, 0.9 m/s or more, 1 m/s or more, 1.25 m/s or more, 1.5 m/s or more, 1.75 m/s or more, 2 m/s or more, 2.25 m/s or more, 2.5 m/s or more, 2.75 m/s or more, 3 m/s or more, 3.5 m/s or more, 4 m/s or more, 4.5 m/s or more, 5 m/s or more, 5.5 m/s or more, 6 m/s or more, 6.5 m/s or more, 7 m/s or more, 7.5 m/s or more, 8 m/s or more, 8.5 m/s or more, or 9 m/s or more). In some examples, the agitator is configured to produce average fluid flow velocities inside the reactor of 10 m/s or less (e.g., 9.5 m/s or less, 9 m/s or less, 8.5 m/s or less, 8 m/s or less, 7.5 m/s or less, 7 m/s or less, 6.5 m/s or less, 6 m/s or less, 5.5 m/s or less, 5 m/s or less, 4.5 m/s or less, 4 m/s or less, 3.5 m/s or less, 3 m/s or less, 2.75 m/s or less, 2.5 m/s or less, 2.25 m/s or less, 2 m/s or less, 1.75 m/s or less, 1.5 m/s or less, 1.25 m/s or less, 1 m/s or less, 0.9 m/s or less, 0.8 m/s or less, 0.7 m/s or less, 0.6 m/s or less, 0.5 m/s or less, 0.45 m/s or less, 0.4 m/s or less, 0.35 m/s or less, 0.3 m/s or less, 0.25 m/s or less, 0.2 m/s or less, 0.15 m/s or less, or 0.1 m/s or less). The fluid flow velocity inside the reactor produced by the agitator can range from any of the minimum values described above to any of the maximum values described above. For example, the agitator can be configured to produce fluid flow velocities inside the reactor of from greater than 0 m/s to 10 m/s (e.g., from greater than 0 to 5 m/s, from 5 to 10 m/s, from greater than 0 to 2.5 m/s, from 2.5 to 5 m/s, from 5 to 7.5 m/s, from 7.5 to 10 m/s, from greater than 0 to 2 m/s, from 2 to 4 m/s, from 4 to 6 m/s, from 6 to 8 m/s, from 8 to 10 m/s, from greater than 0 to 9 m/s, from greater than 0 to 8 m/s, from greater than 0 to 7 m/s, from greater than 0 to 6 m/s, from greater than 0 to 4.5 m/s, from greater than 0 to 4 m/s, from greater than 0 to 3.5 m/s, from greater than 0 to 3 m/s, from greater than 0 to 2.5 m/s, from greater than 0 to 1.5 m/s, from 0.05 to 10 m/s, from 0.1 to 10 m/s, from 0.5 to 10 m/s, from 1 to 10 m/s, from 1.5 to 10 m/s, from 2 to 10 m/s, from 3 to 10 m/s, from 4 to 10 m/s, from 6 to 10 m/s, from 7 to 10 m/s, from 9 to 10 m/s, from 0.05 to 9.5 m/s, from 0.1 to 9 m/s, or from 0.25 to 5 m/s).

(358) Liquid level inside the reactors can be monitored using any suitable means, for example using one or more (e.g., a series of) thermocouples arranged along the internal reactor wall or through non-contact means, such as radar or ultrasonic sensors. For example, a plurality of thermocouples can be arranged vertically along the internal reactor wall. The liquid bath is typically hotter than the vapor in the headspace above it. As the liquid bath level inside a reactor changes, the change can be seen by changing temperatures. Feedstock input and product output can be monitored and/or adjusted based on the observed variations in the liquid bath level.

(359) The liquid volume in each reactor can, for example, comprise 40% or more of the volume of the reactor (e.g., 41% or more, 42% or more, 43% or more, 44% or more, 45% or more, 46% or more, 47% or more, 48% or more, 49% or more, 50% or more, 51% or more, 52% or more, 53% or

more, 54% or more, 55% or more, 56% or more, 57% or more, 58% or more, 59% or more, 60% or more, 61% or more, 62% or more, 63% or more, 64% or more, 65% or more, 66% or more, 67% or more, 68% or more, 69% or more, 70% or more, 71% or more, 72% or more, 73% or more, 74% or more, 75% or more, 76% or more, 77% or more, or 78% or more). In some examples, the liquid volume in the reactor can comprise 80% or less of the volume of the reactor (e.g., 79% or less, 78% or less, 77% or less, 76% or less, 75% or less, 74% or less, 73% or less, 72% or less, 71% or less, 70% or less, 69% or less, 68% or less, 67% or less, 66% or less, 65% or less, 64% or less, 63% or less, 62% or less, 61% or less, 60% or less, 59% or less, 58% or less, 57% or less, 56% or less, 55% or less, 54% or less, 53% or less, 52% or less, 51% or less, 50% or less, 49% or less, 48% or less, 47% or less, 46% or less, 45% or less, 44% or less, 43% or less, or 42% or less). The liquid volume in the reactor can range from any of the minimum values described above to any of the maximum values described above. For example, the liquid volume in the reactor can comprise from 40% to 80% of the volume of the reactor (e.g., from 40% to 60%, from 60% to 80%, from 40% to 50%, from 50% to 60%, from 60% to 70%, from 70% to 80%, from 40% to 75%, from 40% to 70%, from 40% to 65%, from 40% to 55%, from 40% to 45%, from 45% to 80%, from 50% to 80%, from 55% to 80%, from 65% to 80%, from 75% to 680%, from 45% to 75%, or from 50% to 70%).

(360) In some examples, the headspace volume in each reactor comprises 20% or more of the volume of the reactor (e.g., 21% or more, 22% or more, 23% or more, 24% or more, 25% or more, 26% or more, 27% or more, 28% or more, 29% or more, 30% or more, 31% or more, 32% or more, 33% or more, 34% or more, 35% or more, 36% or more, 37% or more, 38% or more, 39% or more, 40% or more, 41% or more, 42% or more, 43% or more, 44% or more, 45% or more, 46% or more, 47% or more, 48% or more, 49% or more, 50% or more, 51% or more, 52% or more, 53% or more, 54% or more, 55% or more, 56% or more, 57% or more, or 58% or more). In some examples, the headspace volume in each reactor comprises 60% or less of the volume of the reactor (e.g., 59% or less, 58% or less, 57% or less, 56% or less, 55% or less, 54% or less, 53% or less, 52% or less, 51% or less, 50% or less, 49% or less, 48% or less, 47% or less, 46% or less, 45% or less, 44% or less, 43% or less, 42% or less, 41% or less, 40% or less, 39% or less, 38% or less, 37% or less, 36% or less, 35% or less, 34% or less, 33% or less, 32% or less, 31% or less, 30% or less, 29% or less, 28% or less, 27% or less, 26% or less, 25% or less, 24% or less, 23% or less, or 22% or less). The headspace volume in the reactor can range from any of the minimum values described above to any of the maximum values described above. For example, the headspace volume in the reactor can comprise from 20% to 60% of the reactor volume (e.g., from 20% to 40%, from 40% to 60%, from 20% to 30%, from 30% to 40%, from 40% to 50%, from 50% to 60%, from 20% to 55%, from 20% to 50%, from 20% to 45%, from 20% to 35%, from 20% to 25%, from 25% to 60%, from 30% to 60%, from 35% to 60%, from 45% to 60%, from 55% to 60%, from 25% to 55%, or from 30% to 50%).

(361) Hydrocarbon vapor generated inside each reactor exits the reactor through a piping or ducting manifold connected to a product recovery system which is described below. In some examples, the reactor vapor pressure is monitored. The type and quality of product output can be controlled to some degree by altering the pressure inside the reactor. Each reactor is connected to a manifold, and vapor flow from each reactor is controlled by a valve designed to operate at the high vapor exit temperature or a down-stream blower/vacuum system, allowing the individual reactors to be maintained as needed between a slight positive pressure and a slight vacuum pressure, depending on reactor performance and the types of hydrocarbon products condensing in the downstream product recovery which operates under a slight vacuum as described below. The piping manifold system also allows inert gases to be introduced when necessary to purge the reactor interior, or displace the liquid bath or vapor headspace in each reactor to another reactor without the use of pumps.

(362) The pressure inside each reactor can, for example, be -7.25 psig or more (e.g., -7 psig or

more, -6.5 psig or more, -6 psig or more, -5.5 psig or more, -5 psig or more, -4.5 psig or more, -4 psig or more, -3.5 psig or more, -3 psig or more, -2.5 psig or more, -2 psig or more, -1.5 psig or more, -1 psig or more, -0.5 psig or more, 0 psig or more, 0.5 psig or more, 1 psig or more, 1.5 psig or more, 2 psig or more, 2.5 psig or more, 3 psig or more, 3.5 psig or more, 4 psig or more, 4.5 psig or more, 5 psig or more, 5.5 psig or more, 6 psig or more, 6.5 psig or more, 7 psig or more, 7.5 psig or more, 8 psig or more, 8.5 psig or more, 9 psig or more, 9.5 psig or more, 10 psig or more, 10.5 psig or more, 11 psig or more, 11.5 psig or more, 12 psig or more, 12.5 psig or more, 13 psig or more, 13.5 psig or more, or 14 psig or more). In some examples, the pressure inside the reactor can be 14.5 psig or less (e.g., 14 psig or less, 13.5 psig or less, 13 psig or less, 12.5 psig or less, 12 psig or less, 11.5 psig or less, 11 psig or less, 10.5 psig or less, 10 psig or less, 9.5 psig or less, 9 psig or less, 8.5 psig or less, 8 psig or less, 7.5 psig or less, 7 psig or less, 6.5 psig or less, 6 psig or less, 5.5 psig or less, 5 psig or less, 4.5 psig or less, 4 psig or less, 3.5 psig or less, 3 psig or less, 2.5 psig or less, 2 psig or less, 1.5 psig or less, 1 psig or less, 0.5 psig or less, 0 psig or less, -0.5 psig or less, -1 psig or less, -1.5 psig or less, -2 psig or less, -2.5 psig or less, -3 psig or less, -3.5 psig or less, -4 psig or less, -4.5 psig or less, -5 psig or less, -5.5 psig or less, -6 psig or less, -6.5 psig or less, or -7 psig or less). The pressure within the reactor can range from any of the minimum values described above to any of the maximum values described above. For example, the pressure inside the reactor can be from -7.25 to 14.5 psig (e.g., from -7.25 to 3.5 psig, from 3.5 to 14.5 psig, from -7.25 to 0 psig, from 0 to 7.25 psig, from 7.25 to 14.5 psig, from -7.25 to 10 psig, from -7.25 to 5 psig, from -5 to 14.5 psig, from 5 to 14.5 psig, from -5 to 10 psig, from -5 to 5 psig, or from -2.5 to 2.5 psig).

(363) The residence time of the feedstock within the reactor (e.g., the time that it takes to pyrolyze) can vary based on a variety of factors. For example, the residence time of the feedstock within the reactor can vary based on the type of reactor, the composition of the feedstock, the temperature within the reactor, the pressure within the reactor, the agitation rate, the amount of char, or a combination thereof.

(364) For example, the residence time of a given polymer comprising the feedstock within the reactor can be 1 second or more (e.g., 2 seconds or more, 3 seconds or more, 4 seconds or more, 5 seconds or more, 10 seconds or more, 15 seconds or more, 20 seconds or more, 25 seconds or more, 30 seconds or more, 35 seconds or more, 40 seconds or more, 45 seconds or more, 50 seconds or more, 55 seconds or more, 1 minute or more, 2 minutes or more, 3 minutes or more, 4 minutes or more, 5 minutes or more, 10 minutes or more, 15 minutes or more, 20 minutes or more, 25 minutes or more, 30 minutes or more, 35 minutes or more, 40 minutes or more, 45 minutes or more, 50 minutes or more, 55 minutes or more, 1 hour or more, 1.5 hours or more, 2 hours or more, 2.5 hours or more, 3 hours or more, 3.5 hours or more, 4 hours or more, 4.5 hours or more, 5 hours or more, 5.5 hours or more, 6 hours or more, 7 hours or more, 8 hours or more, 9 hours or more, 10 hours or more, 12 hours or more, 14 hours or more, 16 hours or more, 18 hours or more, 20 hours or more, or 22 hours or more). In some examples, the residence time of a given polymer comprising the feedstock within the reactor can be 24 hours or less (e.g., 22 hours or more, 20 hours or more, 18 hours or more, 16 hours or more, 14 hours or more, 12 hours or more, 10 hours or more, 9 hours or more, 8 hours or more, 7 hours or more, 6 hours or more, 5.5 hours or more, 5 hours or more, 4.5 hours or more, 4 hours or more, 3.5 hours or more, 3 hours or more, 2.5 hours or more, 2 hours or more, 1.5 hours or more, 1 hour or less, 55 minutes or less, 50 minutes or less, 45 minutes or less, 40 minutes or less, 35 minutes or less, 30 minutes or less, 25 minutes or less, 20 minutes or less, 15 minutes or less, 10 minutes or less, 5 minutes or less, 4 minutes or less, 3 minutes or less, 2 minutes or less, 1 minute or less, 55 seconds or less, 50 seconds or less, 45 seconds or less, 40 seconds or less, 35 seconds or less, 30 seconds or less, 25 seconds or less, 20 seconds or less, 15 seconds or less, 10 seconds or less, or 5 seconds or less). The residence time of a given polymer comprising the feedstock within the reactor can range from any of the minimum values described above to any of the maximum values described above.

(365) For example, the residence time of a given polymer comprising the feedstock within the reactor can be from 1 second to 24 hours (e.g., from 1 second to 12 hours, from 12 hours to 24 hours, from 1 second to 1 minute, from 1 minute to 1 hour, from 1 hour to 24 hours, from 1 second to 1 hour, from 1 hour to 6 hours, from 6 hours to 12 hours, from 12 hours to 18 hours, to 24 hours, from 1 minute to 20 hours, from 1 second to 18 hours, from 1 second to 16 hours, from 1 second to 14 hours, from 1 second to 10 hours, from 1 second to 8 hours, from 1 second to 4 hours, from 1 second to 2 hours, from 1 second to 30 minutes, from 1 second to 15 minutes, from 1 second to 10 minutes, from 1 second to 5 minutes, from 1 minute to 24 hours, from 5 minutes to 24 hours, from 10 minutes to 24 hours, from 15 minutes to 24 hours, from 30 minutes to 24 hours, from 1 hour to 24 hours, from 2 hours to 24 hours, from 4 hours to 24 hours, from 6 hours to 24 hours, from 8 hours to 24 hours, from 10 hours to 24 hours, from 12 hours to 24 hours, from 14 hours to 24 hours, from 16 hours to 24 hours, from 20 ours to 24 hours, from 30 seconds to 22 hours, or from 1 minute to 20 hours).

(366) Inert material that enters the reactors, such as bits of metal and grit, as well as loose char that can be created through the heating process, can optionally be removed by any suitable processing component or step, such as sedimentation, decantation, filtration, sieving, etc.

(367) In some examples, the reactor can further include an additive, such as a catalyst, a diluent, an adsorbent, etc.

(368) FIG. 35 shows a side view of a rotary kiln pyrolysis reactor **1000** according to one implementation. The rotary kiln pyrolysis reactor **1000** is generally configured for pyrolyzing feedstock. In some implementations, the rotary kiln pyrolysis reactor **1000** is configured for receiving and pyrolyzing molten or semi-molten feedstock (e.g., received from an extruder). In other implementations, the rotary kiln pyrolysis reactor **1000** is configured for receiving and pyrolyzing solid or semi-solid feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). Accordingly, the rotary kiln pyrolysis reactor **1000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. FIG. 36 provides a top view of the rotary kiln pyrolysis reactor **1000** shown in FIG. 35. Certain elements depicted in FIG. 35 are also depicted in FIG. 36 and, accordingly, reference to either figure may be regarded as a reference to both figures.

(369) As shown in FIG. 35, the rotary kiln pyrolysis reactor **1000** includes a reactor vessel within which plastic feedstock is deposited and pyrolyzed. In the illustrated implementation, the reactor vessel comprises a reactor barrel **1004**. The reactor barrel **1004** is comprised of a cylindrical body **1012** having a first end **1006** and second end **1008**. In some implementations, the cylindrical body **1012** defines a horizontal longitudinal axis (e.g., parallel to the ground). In other implementations, the cylindrical body **1012** defines a longitudinal axis that is angled (e.g., 10 degrees relative to the ground). The interior of the cylindrical body **1012** defines the reactor vessel's internal volume **1018**. In various implementations, the cylindrical body **1012** may be constructed from steel having a refractory lining (or other materials with suitable structural and thermal properties).

(370) The rotary kiln pyrolysis reactor **1000** further includes a transfer assembly **1026** disposed at the reactor barrel's second end **1008**. The transfer assembly **1026** includes a feedstock inlet **1020**, a vapor outlet **1024**, a sealing interface **1027**, and a plurality of reactor sensors **1030**. As shown in FIG. 35, the feedstock inlet **1020** defines an external opening and extends into the reactor barrel **1004**. In the illustrated implementation, the plastic feedstock (e.g., semi-molten feedstock received from an extruder) is deposited into the reactor vessel's internal volume **1018** by way of the feedstock inlet **1020**. In various implementations, the feedstock inlet's external inlet opening is positioned outside of the reactor barrel **1004** and defines an aperture through which plastic feedstock may enter the feedstock inlet **1020**. The feedstock inlet **1020**, which may comprise, for example, a pipe, extends into the internal volume **1018** and includes an outlet opening positioned

within the reactor barrel's internal volume **1018**. As will be appreciated from FIG. 35, when plastic feedstock (e.g., semi-molten feedstock) is directed through the feedstock inlet **1020** via its inlet opening, the plastic feedstock will be directed through the feedstock inlet and deposited within the reactor vessel's internal volume **1018** for processing.

(371) The transfer assembly's vapor outlet **1024** defines an internal opening (positioned within the reactor barrel's internal volume **1018**) and an external opening (positioned outside of the reactor barrel **1004**). The transfer assembly's vapor outlet **1024**, which may comprise, for example, a pipe, extends into the reactor barrel **1004** at the reactor barrel's second end **1008** and enables vapor produced during pyrolysis of the feedstock within the reactor barrel **1004** to exit the reactor barrel **1004**.

(372) The rotary kiln pyrolysis reactor **1000** further comprises a drive motor **1016** and drive gear **1017** configured for rotating the reactor barrel **1004** about its longitudinal axis. In the illustrated implementation of FIG. 35, the reactor barrel **1004** is rotatably mounted on a plurality of roller supports **1023**. As shown in FIG. 35, a plurality of rollers **1025** are disposed on the exterior wall of the reactor barrel's cylindrical body **1012** and configured to enable the reactor barrel **1004** to rotate about its longitudinal axis. In various implementations, the reactor barrel **1004** may be rotated via a chain drive (e.g., such that a chain links the drive motor **1016** to the drive gear **1017** disposed on the reactor barrel **1004**). Various implementations of the reactor barrel **1004** are configured for continuously rotating such that the liquid plastic inside the reactor vessel is kept in continuous motion. In this way, the reactor barrel's rotation provides sufficient movement of the liquid plastic to acquire heat for pyrolysis to occur. For example, in one implementation, the reactor barrel **1004** is continuously rotated during the pyrolysis process.

(373) As shown in FIG. 35, the transfer assembly **1026** includes a sealing interface **1027**. In various implementations, the sealing interface **1027** is configured to provide a seal between the reactor barrel's second end **1008** and the transfer assembly **1026**. In this way, the reactor barrel's internal volume **1018** remains sealed and enclosed as the reactor barrel **1004** rotates about its longitudinal axis and the transfer assembly **1026** remains in a fixed position.

(374) In various implementations, the rotary kiln pyrolysis reactor **1000** includes a heating device configured for heating the internal volume **1018** of the reactor barrel **1004**. In the illustrated implementation, the heating device comprises a burner assembly **1013** disposed at the reactor barrel's first end **1006**. The burner assembly **1013** comprises a burner pipe **1015** and a kiln hood **1014**. As shown in FIG. 35, the burner assembly **1013** is configured as a direct fired kiln system in which the burner pipe **1015** emits a flame that heats the reactor barrel's **1004** internal volume **1018**. In the illustrated implementation, the burner pipe **1015** is oriented in a counter-current direction. In other implementations, the burner pipe **1015** may be oriented in a co-current direction. In further implementations, the burner assembly **1013** may be configured as an indirect fired kiln system for heating the reactor barrel **1004**.

(375) In various implementations, the burner assembly **1013** is generally configured to provide the heat needed to raise temperatures inside the reactor barrel **1004** to a point where depolymerization takes place. For example, burner pipe **1015** may be controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock within the reactor barrel **1004**. In combination with continuous rotation of the reactor barrel **1004** (e.g., driven by the drive motor **1016** and drive gear **1017**) the pyrolysis reaction within the reactor barrel **1004** can be controlled to provide a desired reaction temperature and energy density (kW/lb.).

(376) As shown in FIG. 35, the rotary kiln pyrolysis reactor **1000** includes a vapor outlet **1024**. As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor. Accordingly, the reactor's vapor outlet **1024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **1000** and thus extends upwardly from the transfer assembly **1026**. In various implementations, the vapor

outlet **1024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **35**, the vapor outlet **1024** is configured to direct vapor exiting the reactor barrel **1004** following pyrolysis to a product collection system **1036** configured for product recovery (e.g., oil, wax, gas or combinations thereof as described herein).

(377) In the illustrated implementation of FIG. **35**, the reactor's transfer assembly **1026** includes a plurality of reactor sensors **1030**. In various implementations, the reactor sensors **1030** may be configured for measuring the dynamic properties of the liquid plastic within the reactor, output and dynamic properties of the heating system, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production) and a variety of other variables. For example, in various implementations, the reactor sensors **1030** may comprise thermocouples, pressure sensors, flow meters, and the like. In this way, feedstock input (e.g., from an extruder) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic within the reactor.

(378) In various implementations, a plurality of rotary kiln pyrolysis reactors **1000** can also be provided for use in the production of wax, oil, gas, or combinations thereof. For example, in one implementation, three rotary kiln pyrolysis reactors **1000** are used and can be operational in any combination with one another (e.g., such that all three pyrolysis reactors **1000** are processing feedstock simultaneously, or such that two of the pyrolysis reactors **1000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance).

(379) FIG. **37** shows a side view of a screw pyrolysis reactor **2000** according to one implementation. The screw pyrolysis reactor **2000** is generally configured for pyrolyzing feedstock. In some implementations, the screw pyrolysis reactor **2000** is configured for receiving and pyrolyzing semi-molten feedstock (e.g., received from an extruder). In other implementations, the screw pyrolysis reactor **2000** is configured for receiving and pyrolyzing solid or semi-solid plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). Accordingly, the screw pyrolysis reactor **2000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. FIG. **38** provides a top view of the screw pyrolysis reactor **2000** shown in FIG. **37**. Certain elements depicted in FIG. **37** are also depicted in FIG. **38** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(380) As shown in FIG. **37**, the screw pyrolysis reactor **2000** includes a reactor vessel within which plastic feedstock is deposited and pyrolyzed. In the illustrated implementation, the reactor vessel comprises a reactor barrel **2010**. The reactor barrel **2010** is comprised of a cylindrical body **2012** having a first end **2006** and second end **2008**. In some implementations, the cylindrical body **2012** defines a horizontal longitudinal axis (e.g., parallel to the ground). The interior of the cylindrical body **2012** defines the reactor vessel's internal volume **2018**. In various implementations, the cylindrical body **2012** may be constructed from steel (or other materials with suitable structural and thermal properties).

(381) The screw pyrolysis reactor **2000** further includes a screw **2014** disposed within the reactor barrel's internal volume **2018**. As shown in FIG. **37**, the screw **2014** is oriented horizontally and extends longitudinally through the reactor barrel's internal volume **2018** (e.g., such that a longitudinal axis of the screw **2014** is parallel to the longitudinal axis of the reactor barrel **2010**). In various implementations, the screw **2014** is configured to rotate (e.g., about its longitudinal axis) and transfer plastic feedstock laterally through the reactor barrel's internal volume **2018**. As explained in greater detail herein, the reactor barrel's internal volume **2018** is heated to drive pyrolysis of the plastic feedstock as the screw **2014** transfers the feedstock through the reactor

barrel **2010**.

(382) The screw pyrolysis reactor **2000** further comprises a drive motor and gear assembly **2016** configured for rotating the screw **2014** about its longitudinal axis. In the illustrated implementation of FIG. **35**, the screw **2014** includes a helical protrusion that, when rotating, transfers the plastic feedstock through the reactor barrel **2010** (e.g., from the first end **2006** towards the second end **2008**). Accordingly, by controlling the speed of the motor and gear assembly **2016**, the rotational speed of the screw may be controlled to dictate the velocity of the plastic feedstock as it is transferred through the reactor barrel **2010**. Various implementations of the screw **2014** are configured for continuously rotating such that the liquid plastic inside the reactor barrel **2010** is kept in continuous motion. In this way, the screw's rotation provides sufficient movement of the liquid plastic to acquire heat for pyrolysis to occur as it is transferred laterally through the reactor barrel **2010**. For example, in one implementation, the reactor barrel **1004** is continuously rotated during the pyrolysis process.

(383) The screw pyrolysis reactor **2000** further comprises a feedstock inlet **2020**, a vapor outlet **2024**, one or more ports **2025**, one or more external heating elements **2034**, a discharge manifold **2022**, and a plurality of reactor sensors **2030**. As shown in FIG. **37**, the feedstock inlet **2020** defines an external opening and extends into the reactor barrel **2010**. In the illustrated implementation, the plastic feedstock (e.g., semi-molten feedstock received from an extruder or solid feedstock) is deposited into the reactor vessel's internal volume **2018** by way of the feedstock inlet **2020**. In various implementations, the feedstock inlet's external inlet opening is positioned outside of the reactor barrel **2010** and defines an aperture through which plastic feedstock may enter the feedstock inlet **2020**. The feedstock inlet **2020**, which may comprise, for example, a pipe, extends into the internal volume **2018** and includes an outlet opening positioned within the reactor barrel's internal volume **2018**. As will be appreciated from FIG. **37**, when plastic feedstock (e.g., semi-molten feedstock or solid feedstock) is directed through the feedstock inlet **2020** via its inlet opening, the plastic feedstock will be directed through the feedstock inlet and deposited within the reactor vessel's internal volume **2018** for processing.

(384) As shown in FIG. **37**, the screw pyrolysis reactor **2000** includes a plurality of heating elements **2034** configured for heating the internal volume **2018** of the reactor barrel **2010**. In the illustrated implementation, the heating elements **2034** comprise electric heaters positioned externally around the reactor barrel **2010**. When activated, the transfer of heat from the electric heaters **2034** through the reactor barrel's cylindrical body **2012** thereby heats the internal volume **2018** of the reactor barrel **2010**.

(385) In various implementations, the heating elements **2034** are generally configured to provide the heat needed to raise temperatures inside the reactor barrel **2010** to a point where depolymerization takes place. For example, the heating elements **2034** may be controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock within the reactor barrel **2010**. In combination with continuous rotation of the screw **2014** (e.g., driven by the drive motor and gear assembly **2016**), which transfers the liquid plastic through the reactor barrel **2010**, the pyrolysis reaction within the reactor barrel **2010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.). Furthermore, in implementations in which heating of the reactor barrel **2010** is provided exclusively by the electric heating elements **2034**, the screw pyrolysis reactor **2000** may be configured for driving the pyrolysis process using only electricity (e.g., without using gas as a direct heat source).

(386) In various other implementations, the plurality of heating elements **2034** may comprise gas powered heaters positioned around the reactor barrel **2010**. In further implementations, the screw pyrolysis reactor **2000** may also include one or more heat inlets positioned around the reactor barrel **2010**. In such implementations, the heat inlets may be configured for receiving heated elements (e.g., heated ceramic balls) deposited into the reactor barrel's internal volume **2018** for transferring heat directly to the liquid plastic feedstock within the reactor barrel **2010**. In other implementations,

the heat inlets may be configured for receiving heated gas directed into (or around) the reactor barrel **2010** to heat the reactor barrel's internal volume **2018**.

(387) As shown in FIG. **37**, the screw pyrolysis reactor **2000** further includes one or more vapor outlet ports **2025**. In various implementations, the ports **2025** may be positioned and configured to allow certain pre-pyrolysis vapors and/or gases produced from the plastic feedstock during the heating process to escape from the reactor barrel **2010**. For example, in various implementations, the ports may be configured to allow air, steam, and other low melting point volatiles to exit the reactor barrel **2010**. In certain implementations, such as when a vented extruder is used to feed semi-molten feedstock into the screw pyrolysis reactor **2000**, the ports **2025** may be omitted from the screw pyrolysis reactor **2000**.

(388) The screw pyrolysis reactor **2000** further includes a discharge manifold **2022** positioned at the reactor barrel's second end **2008**. In various implementations, the discharge manifold **2022** is configured to provide an outlet for material within the reactor barrel **2010**. For example, the discharge manifold **2022** may be used to transfer or otherwise remove liquid plastic (or other material generated during the pyrolysis process) from the reactor barrel **2010**. Accordingly, various implementations of the discharge manifold **2022** may include a sealable discharge opening (e.g., a port which can be selectively opened or sealed and closed).

(389) As shown in FIG. **37**, the screw pyrolysis reactor **2000** also includes a vapor outlet **2024**. In various implementations, the vapor outlet **2024** defines an internal opening (positioned within the reactor barrel's internal volume **2018**) and an external opening (positioned outside of the reactor barrel **2010**). The vapor outlet **2024**, which may comprise, for example, a pipe, extends into the reactor barrel **2010** at the reactor barrel's second end **2008** and enables vapor produced during pyrolysis of the plastic feedstock within the reactor barrel **2010** to exit the reactor barrel **2010**.

(390) As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor. Accordingly, the reactor's vapor outlet **2024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **2000** and thus extends upwardly from the reactor barrel **2010**. In various implementations, the vapor outlet **2024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **37**, the vapor outlet **2024** is configured to direct vapor exiting the reactor barrel **2010** following pyrolysis to a product collection system **2036** (e.g., production of wax, oil, gas, or combinations thereof as described herein).

(391) In the illustrated implementation of FIG. **37**, the screw pyrolysis reactor **2000** further includes a plurality of reactor sensors **2030**. In various implementations, the reactor sensors **2030** may be configured for measuring dynamic properties of the liquid plastic within the reactor, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production). For example, in various implementations, the reactor sensors **2030** may comprise thermocouples, pressure sensors, flow meters, and the like. In this way, feedstock input (e.g., from the extruder **400**) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic within the reactor.

(392) In various implementations, a plurality of screw pyrolysis reactors **2000** can also be provided for use in the production of wax, oil, gas, or combinations thereof. For example, in one implementation, three screw pyrolysis reactors **2000** are used and can be operational in any combination with one another (e.g., such that all three pyrolysis reactors **2000** are processing feedstock simultaneously, or such that two of the pyrolysis reactors **2000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance).

(393) FIG. **39** shows a side view of a fluidized bed pyrolysis reactor **3000** according to one implementation. The fluidized bed pyrolysis reactor **3000** is generally configured for pyrolyzing

feedstock. In some implementations, the fluidized bed pyrolysis reactor **3000** is configured for receiving and pyrolyzing semi-molten feedstock (e.g., received from an extruder). In other implementations, the fluidized bed pyrolysis reactor **3000** is configured for receiving and pyrolyzing solid or semi-solid plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). Accordingly, the fluidized bed pyrolysis reactor **3000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. FIG. **40** provides a top view of the fluidized bed pyrolysis reactor **3000** shown in FIG. **39**. Certain elements depicted in FIG. **39** are also depicted in FIG. **40** and, accordingly, reference to either figure may be regarded as a reference to both figures. (394) As shown in FIG. **39**, the fluidized bed pyrolysis reactor **3000** includes a reactor vessel **3010** within which plastic feedstock is deposited and pyrolyzed. The reactor vessel **3010** is comprised of a cylindrical body **3012**, a first ellipsoidal head **3014** disposed at an upper end of the cylindrical body **3012** (herein the upper ellipsoidal head **3014**), and a second ellipsoidal head **3016** disposed at a lower end of the cylindrical body **3012** (herein the lower ellipsoidal head **3016**). Together, the cylindrical body **3012** and ellipsoidal heads **3014**, **3016** define an internal volume **3018** of the reactor vessel **3010** (shown in FIG. **39**). In various implementations, the cylindrical body **3012** and ellipsoidal heads **3014**, **3016** may be constructed from stainless steel (or other materials with suitable structural and thermal properties).

(395) The fluidized bed pyrolysis reactor **3000** further comprises a catalyst inlet **3020**, pressurized feedstock inlet **3021**, a discharge manifold **3022**, a vapor outlet **3024**, a distributor **3028**, a plurality of reactor sensors **3030**, one or more external heating elements **3034**, and a product collection system **3036**. As shown in FIG. **39**, the pressurized feedstock inlet **3021** defines an external opening and extends into the reactor vessel **3010**. In the illustrated implementation, the plastic feedstock (e.g., semi-molten feedstock received from an extruder) is deposited into the reactor vessel's internal volume **3018** by way of the feedstock inlet **3021**. In various implementations, the feedstock inlet's external inlet opening is positioned outside of the reactor vessel **3010** and defines an aperture through which plastic feedstock may enter the feedstock inlet **3021**. The feedstock inlet **3021**, which may comprise, for example, a pipe, extends into the internal volume **3018** and includes an outlet opening positioned within the reactor vessel's internal volume **3018**. As will be appreciated from FIG. **39**, when plastic feedstock (e.g., semi-molten feedstock) is directed through the feedstock inlet **3021** via its inlet opening, the plastic feedstock will be directed through the feedstock inlet and deposited within the reactor vessel's internal volume **3018** for processing.

(396) In various implementations, the pressurized feedstock inlet **3021** is configured to inject molten or semi-molten feedstock at pressure into the reactor vessel **3010**. As depicted in FIG. **39**, the pressurized feedstock inlet's outlet opening is positioned in a lower portion of the reactor vessel's internal volume **3018** and below a distributor **3028**. In various implementations, the distributor **3028** comprises a porous plate defining a plurality of apertures through which liquid plastic may flow through. The pressure at which the plastic feedstock is injected into the reactor vessel **3010** forces the liquid plastic feedstock upwardly, through the apertures defined in the distributor **3028**, and further into the reactor vessel's internal volume **3018**. The distributor **3028** divides the liquid plastic into a plurality of streams, thereby exposing a greater surface area of the liquid plastic within the reactor vessel **3018**. Furthermore, the distributor's apertures are dimensioned such that the catalyst provided within the reactor vessel **3010** cannot pass through the distributor **3028**.

(397) As shown in FIG. **39**, the catalyst inlet **3020** is positioned at an upper portion of the reactor vessel **3010** and substantially above the distributor **3028**. As shown in FIG. **39**, the catalyst inlet **3020** defines an external opening and extends into the reactor vessel **3010**. In the illustrated implementation, a catalyst (e.g., Zeolites, metal catalysts, and the like) is deposited into the reactor

vessel's internal volume **3018** by way of the catalyst inlet **3020**. In various implementations, the catalyst inlet's opening is positioned outside of the reactor vessel **3010** and defines an aperture through which a catalyst material may enter the catalyst inlet **3020**. The feedstock inlet **3021**, which may comprise, for example, a pipe, extends into the internal volume **3018** and includes an outlet opening positioned within the reactor vessel's internal volume **3018**. As will be appreciated from FIG. **39**, when a catalyst is directed through the catalyst inlet **3020** via its inlet opening, the catalyst will be directed through the catalyst inlet and deposited within the reactor vessel's internal volume **3018**.

(398) In various implementations, the fluidized bed pyrolysis reactor **3000** is configured such that the liquid plastic feedstock is directed into the reactor vessel **3010** (via the feedstock inlet **3021** and through the distributor **3028**) with a velocity that is sufficient to reach incipient fluidization. In other words, the velocity of the plastic feedstock is sufficient to balance the weight of the catalyst or catalytic material being deposited into the reactor vessel **3010** via the catalyst inlet **3020** (e.g., such that the bath of liquid plastic and catalyst mix and swirl within the reactor vessel **3010**). In this way, the reactor vessel's internal volume **3018** comprises a fluidized bed, which includes the catalyst and liquid plastic feedstock. In various implementations, the catalyst may be selected to accelerate the rate of pyrolysis within the reactor vessel **3010** and/or lower the temperature at which pyrolysis occurs within the reactor vessel **3010**.

(399) As shown in FIG. **39**, the fluidized bed pyrolysis reactor **3000** includes a plurality of external heating elements **3034** configured for heating the internal volume **3018** of the reactor vessel **3010**. In various implementations, the external heating elements **3034** may comprise electric heaters positioned externally around the reactor vessel **3010**. When activated, the transfer of heat from the electric heaters **3034** through the reactor vessel's cylindrical body **3012** thereby heats the internal volume **3018** of the reactor vessel **3010**.

(400) In various implementations, the heating elements **3034** are generally configured to provide the heat needed to raise temperatures inside the reactor vessel **3010** to a point where depolymerization takes place. For example, the heating elements **3034** may be controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock within the reactor vessel **3010**. In particular, the pyrolysis reaction within the reactor vessel **3010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.). Furthermore, in implementations in which heating of the reactor vessel **3010** is provided exclusively by the electric heating elements **3034**, the fluidized bed pyrolysis reactor **3000** may be configured for driving the pyrolysis process using only electricity (e.g., without using gas as a direct heat source).

(401) In various other implementations, the external heating elements **3034** may comprise gas powered heaters positioned around the reactor vessel **3010**. In further implementations, one or more heat inlets may be positioned around the reactor vessel **3010**. In such implementations, the heat inlets may be configured for receiving heated elements (e.g., heated ceramic balls) deposited into the reactor vessel's internal volume **3018** for transferring heat directly to the liquid plastic feedstock within the reactor vessel **3010**. In other implementations, the heat inlets may be configured for receiving heated gas directed around or within the reactor vessel **3010** to heat the reactor vessel's internal volume **3018**.

(402) The fluidized bed pyrolysis reactor **3000** further includes a discharge manifold **3022**. In various implementations, the discharge manifold **3022** is configured to provide an outlet for material within the reactor vessel **3010**. For example, the discharge manifold **3022** may be used to transfer or otherwise remove liquid plastic (or other material generated during the pyrolysis process) from the reactor vessel **3010**. Accordingly, various implementations of the discharge manifold **3022** may include a sealable discharge opening (e.g., a port which can be selectively opened or sealed and closed).

(403) As shown in FIG. **39**, the fluidized bed pyrolysis reactor **3000** also includes a vapor outlet

3024. In various implementations, the vapor outlet **3024** defines an internal opening (positioned within the reactor vessel's internal volume **3018**) and an external opening (positioned outside of the reactor vessel **3010**). The vapor outlet **3024**, which may comprise, for example, a pipe, extends into the reactor vessel **3010** through the reactor vessel's ellipsoidal head **3014** and enables vapor produced during pyrolysis of the plastic feedstock within the reactor vessel **3010** to exit the reactor vessel **3010**.

(404) As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor. Accordingly, the reactor's vapor outlet **3024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **3000** and thus extends upwardly from the reactor vessel **3010**. In various implementations, the vapor outlet **3024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **39**, the vapor outlet **3024** is configured to direct vapor exiting the reactor vessel **3010** following pyrolysis to a product collection system **3036** configured for product recovery (e.g., production of wax, oil, gas, or combinations thereof as described herein).

(405) In the illustrated implementation of FIG. **39**, the fluidized bed pyrolysis reactor **3000** further includes a plurality of reactor sensors **3030**. In various implementations, the reactor sensors **3030** may be configured for measuring dynamic properties of the liquid plastic within the reactor vessel **3010**, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production). For example, in various implementations, the reactor sensors **3030** may comprise thermocouples, pressure sensors, flow meters, and the like. In this way, feedstock input (e.g., from the extruder **400**) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic within the reactor **3000**.

(406) In various implementations, a plurality of fluidized bed pyrolysis reactor **3000** can also be provided for use in the production of wax, oil, gas, or combinations thereof. For example, in one implementation, three fluidized bed pyrolysis reactor **3000** are used and can be operational in any combination with one another (e.g., such that all three pyrolysis reactors **3000** are processing feedstock simultaneously, or such that two of the pyrolysis reactors **3000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance).

(407) In various other implementations, the fluidized bed pyrolysis reactor **3000** may be alternatively configured as a packed bed reactor. In such implementations, the distributor **3028** may be configured for supporting a solid catalytic material through which liquid plastic is forced upwardly (into the reactor vessel **3010**).

(408) FIG. **41** shows a side view of a batch pyrolysis reactor **4000** according to one implementation. The batch pyrolysis reactor **4000** is generally configured for pyrolyzing feedstock in batches (e.g., not continuously). The batch pyrolysis reactor **4000** is configured for receiving and pyrolyzing semi-molten feedstock (e.g., received from an extruder). In other implementations, the batch pyrolysis reactor **4000** is configured for receiving and pyrolyzing solid or semi-solid plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). Accordingly, the batch pyrolysis reactor **4000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. FIG. **42** provides a top view of the batch pyrolysis reactor **4000** shown in FIG. **41**. Certain elements depicted in FIG. **41** are also depicted in FIG. **42** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(409) As shown in FIG. **41**, the batch pyrolysis reactor **4000** includes a reactor vessel **4010** within which plastic feedstock is deposited and pyrolyzed. The reactor vessel **4010** is comprised of a

cylindrical body **4012**, a removable head **4014** disposed at an upper end of the cylindrical body **4012** (herein the upper head **3014**), and a base **4016** disposed at a lower end of the cylindrical body **4012**. Together, the cylindrical body **4012**, removable head **4014**, and the base **4016** define an internal volume **4018** of the reactor vessel **4010** (shown in FIG. **41**). In various implementations, the cylindrical body **4012**, removable head **4014**, and the base **4016** may be constructed from stainless steel (or other materials with suitable structural and thermal properties).

(410) In various implementations, the batch pyrolysis reactor **4000** is configured for pyrolyzing plastic feedstock in batches (e.g., one by one) Accordingly, the reactor vessel's removable head **4014** is secured to the upper portion of the reactor vessel **4010** by a seal interface **4026** and seal interface fasteners **4027**. The combination of the seal interface **4026** and fasteners **4027** (e.g., high-strength fasteners) ensures that, when the removable head **4014** is secured to the upper portion of the reactor vessel **4010**, the vessel **4010** can maintain desired conditions during pyrolysis.

(411) The batch pyrolysis reactor **4000** further comprises a discharge manifold **4022**, a vapor outlet **4024**, a seal interface **4026**, seal interface fasteners **4027**, a plurality of reactor sensors **4030**, one or more external heating elements **4034**, and a product collection system **4036**. In the illustrated implementation, the plastic feedstock is deposited into the reactor vessel's internal volume **4018** by way of the removable head **4020** for processing.

(412) As shown in FIG. **41**, the batch pyrolysis reactor **4000** includes a plurality of external heating elements **4034** configured for heating the internal volume **4018** of the reactor vessel **4010**. In the illustrated implementation, the external heating elements **4034** comprise both electric heaters (positioned externally around the sides of the reactor vessel's cylindrical body **4012** in FIG. **41**) and gas heaters (positioned beneath the reactor vessel's base **4016** in FIG. **41**). When activated, the transfer of heat from the heating elements **4034** through the reactor vessel's cylindrical body **4012** thereby heats the internal volume **4018** of the reactor vessel **4010**. In other implementations, the heating elements **4034** may comprise all electric, all gas, or a combination of gas and electric heating elements and may be positioned internally or externally to the reactor vessel **4010**.

(413) In various implementations, the heating elements **4034** are generally configured to provide the heat needed to raise temperatures inside the reactor vessel **4010** to a point where depolymerization takes place. For example, the heating elements **4034** may be controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock bath within the reactor vessel **4010**. In particular, the pyrolysis reaction within the reactor vessel **4010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.).

(414) In further implementations, one or more heat inlets may be positioned around the reactor vessel **4010**. In such implementations, the heat inlets may be configured for receiving heated elements (e.g., heated ceramic balls) deposited into the reactor vessel's internal volume **4018** for transferring heat directly to the liquid plastic feedstock within the reactor vessel **4010**. In other implementations, the heat inlets may be configured for receiving heated gas directed around or within the reactor vessel **4010** to heat the reactor vessel's internal volume **4018**.

(415) The batch pyrolysis reactor **4000** further includes a discharge manifold **4022**. In various implementations, the discharge manifold **4022** is configured to provide an outlet for material within the reactor vessel **4010**. For example, the discharge manifold **4022** may be used to transfer or otherwise remove liquid plastic (or other material generated during the pyrolysis process) from the reactor vessel **4010**. Accordingly, various implementations of the discharge manifold **4022** may include a sealable discharge opening (e.g., a port which can be selectively opened or sealed and closed).

(416) As shown in FIG. **41**, the batch pyrolysis reactor **4000** also includes a vapor outlet **4024**. In various implementations, the vapor outlet **4024** defines an internal opening (positioned within the reactor vessel's internal volume **4018**) and an external opening (positioned outside of the reactor vessel **4010**). The vapor outlet **4024**, which may comprise, for example, a pipe, extends into the

reactor vessel **4010** through the reactor vessel's removable head **4014** and enables vapor produced during pyrolysis of the plastic feedstock within the reactor vessel **4010** to exit the reactor vessel **4010**.

(417) As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor. Accordingly, the reactor's vapor outlet **4024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **4000** and thus extends upwardly from the reactor vessel **4010**. In various implementations, the vapor outlet **4024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **41**, the vapor outlet **4024** is configured to direct vapor exiting the reactor vessel **4010** following pyrolysis to a product collection system **4036** configured for product recovery (e.g., production of wax, oil, gas, or combinations thereof as described herein).

(418) In the illustrated implementation of FIG. **41**, the batch pyrolysis reactor **4000** further includes a plurality of reactor sensors **4030**. In various implementations, the reactor sensors **4030** may be configured for measuring dynamic properties of the liquid plastic bath within the reactor vessel **4010**, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production). For example, in various implementations, the reactor sensors **4030** may comprise thermocouples, pressure sensors, flow meters, and the like. In this way, feedstock input (e.g., from the extruder **400**) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic bath within the reactor **4000**.

(419) In various implementations, a plurality of batch pyrolysis reactors **4000** can also be provided for use in the production of wax, oil, gas, or combinations thereof. For example, in one implementation, three batch pyrolysis reactors **4000** are used and can be operational in any combination with one another (e.g., such that all three pyrolysis reactors **4000** are processing feedstock simultaneously, or such that two of the pyrolysis reactors **4000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance).

(420) FIG. **43** shows a continuously stirred pyrolysis reactor **5000** according to one implementation. The continuously stirred pyrolysis reactor **5000** is generally configured for pyrolyzing feedstock (e.g., semi-molten feedstock received from an extruder). Accordingly, the continuously stirred pyrolysis reactor **5000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. FIG. **44** provides a top view of the continuously stirred pyrolysis reactor **5000** shown in FIG. **43**. Certain elements depicted in FIG. **43** are also depicted in FIG. **44** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(421) As shown in FIG. **43**, the continuously stirred pyrolysis reactor **5000** includes a reactor vessel **5010** within which solid, molten, or semi-molten feedstock is deposited and pyrolyzed. The reactor vessel **5010** is comprised of a cylindrical body **5012**, a first ellipsoidal head **5014** disposed at an upper end of the cylindrical body **5012** (herein the upper ellipsoidal head **5014**), and a second ellipsoidal head **5016** disposed at a lower end of the cylindrical body **5012** (herein the lower ellipsoidal head **5016**). Together, the cylindrical body **5012** and ellipsoidal heads **5014**, **5016** define an internal volume **5018** of the reactor vessel **5010** (shown in FIG. **43**). In various implementations, the cylindrical body **5012** and ellipsoidal heads **5014**, **5016** may be constructed from stainless steel (or other materials with suitable structural and thermal properties). As shown in FIG. **43**, the reactor vessel **5010** may be mounted in a substantially upright position (e.g., such that its longitudinal axis is substantially vertical).

(422) The reactor vessel's cylindrical body **5012** includes an inlet port **5020**, a discharge manifold **5022**, a vapor outlet **5024**, and a plurality of reactor sensors **5030**. Semi-molten feedstock (e.g.,

received from an extruder) is deposited into the reactor vessel's internal volume **5018** by way of the inlet port **5020**. In various implementations, the inlet port **5020** defines an external opening and extends into the reactor vessel **5010**. In the illustrated implementation, the plastic feedstock (e.g., semi-molten feedstock received from an extruder) is deposited into the reactor vessel's internal volume **5018** by way of the inlet port **5020**. In various implementations, the inlet port's external inlet opening is positioned outside of the reactor vessel **5010** and defines an aperture through which plastic feedstock may enter the inlet port **5020**. The inlet port **5020**, which may comprise, for example, a pipe, extends into the internal volume **5018** and includes an outlet opening positioned within the reactor vessel's internal volume **5018**. As will be appreciated from FIG. **43**, when plastic feedstock (e.g., semi-molten feedstock) is directed through the inlet port **5020** via its inlet opening, the plastic feedstock will be directed through the inlet port and deposited within the reactor vessel's internal volume **5018** for processing. As the continuously stirred pyrolysis reactor **5000** is configured for continuous operation, in certain implementations, the plastic feedstock may be deposited into the reactor's internal volume **5018** continuously (e.g., such that as the plastic feedstock pyrolyzes and vapor exits the reactor, additional plastic feedstock is deposited into the reactor **5000** to continue the process).

(423) The continuously stirred pyrolysis reactor **5000** further includes a discharge manifold **5022**. In various implementations, the discharge manifold **5022** is configured to provide an outlet for material within the reactor vessel **5010**. For example, the discharge manifold **5022** may be used to transfer or otherwise remove liquid plastic (or other material generated during the pyrolysis process) from the reactor vessel **5010**. Accordingly, various implementations of the discharge manifold **5022** may include a sealable discharge opening (e.g., a port which can be selectively opened or sealed and closed).

(424) As shown in FIG. **43**, the continuously stirred pyrolysis reactor **5000** also includes a vapor outlet **5024**. In various implementations, the vapor outlet **5024** defines an internal opening (positioned within the reactor vessel's internal volume **5018**) and an external opening (positioned outside of the reactor vessel **5010**). The vapor outlet **5024**, which may comprise, for example, a pipe, extends into the reactor vessel **5010** through the reactor vessel's upper ellipsoidal head **5014** and enables vapor produced during pyrolysis of the plastic feedstock within the reactor vessel **5010** to exit the reactor vessel **5010**.

(425) As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor. Accordingly, the reactor's vapor outlet **5024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **5000** and thus extends upwardly from the reactor vessel **5010**. In various implementations, the vapor outlet **5024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **43**, the vapor outlet **5024** is configured to direct vapor exiting the reactor vessel **5010** following pyrolysis to a product collection system **5036** configured for product recovery (e.g., production of wax, oil, gas, or combinations thereof as described herein).

(426) As shown in FIG. **43**, the continuously stirred pyrolysis reactor **5000** includes a plurality of external gas heating elements **5034** configured for heating the internal volume **5018** of the reactor vessel **5010**. In the illustrated implementation, the external heating elements **5034** are gas heaters positioned both laterally on the sides of the reactor vessel's cylindrical body **5012** and beneath the reactor's lower ellipsoidal head **5016** (proximate to the lower portion of the reactor vessel **5010**). When activated, the transfer of heat from the gas heating elements **5034** through the reactor vessel's cylindrical body **5012** thereby heats the internal volume **5018** of the reactor vessel **5010**.

(427) In various implementations, the gas heating elements **5034** are generally configured to provide the heat needed to raise temperatures inside the reactor vessel **5010** to a point where depolymerization takes place. For example, the heating elements **5034** may be controlled to

provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock bath within the reactor vessel **5010**. In particular, the pyrolysis reaction within the reactor vessel **5010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.).

(428) The reactor vessel's upper ellipsoidal head **5014** defines an agitator drive mount configured to enable a motor **5026** to be coupled to an agitator **5028** positioned within the pyrolysis reactor **5000**. As shown and described herein with respect to FIGS. **43** and **44**, the motor-driven agitator **5028** is disposed within the reactor vessel **5010** and is configured to agitate the liquid plastic bath within the vessel **5010** during pyrolysis. In various implementations, the agitator drive mount includes a sealed agitator opening through which the agitator's drive shaft may be accessed and coupled to the drive motor **5026**. In particular, the agitator opening is configured to provide a seal between the agitator's drive shaft and the agitator drive mount in order to maintain desired operating conditions within the reactor vessel **5010**. For example, in one implementation, the agitator opening may comprise a mechanical seal, bellows-style seal, split-ring stuff box, stuffing box-style seal, or the like.

(429) In various implementations, the agitator **5028** is rotated by the electric motor **5026** and configured to produce liquid flow velocities inside the reactor vessel **5010** such that the heat necessary for depolymerization is distributed throughout the liquid plastic bath. Furthermore, the agitator **5028** is configured to circulate the liquid plastic bath in a manner that avoids long residence times at heated surfaces.

(430) As shown in FIG. **43**, the agitator **5028** includes a vertical drive shaft and a plurality of impellers **5029** spaced along the length of the drive shaft. In the illustrated implementation, the agitator's drive shaft is vertically oriented within the reactor vessel **5010** (e.g., such that the longitudinal axis of the drive shaft is parallel with the longitudinal axis of the reactor vessel's cylindrical body **5012**). Additionally, the drive shaft is centrally located within the reactor vessel **5010** (e.g., such that the longitudinal axis of the drive shaft **5042** is aligned with the longitudinal axis of the cylindrical body **5012**). The drive shaft includes an upper end, which is operatively coupled to the drive motor **5026** via the agitator drive mount (e.g., such that the drive shaft's upper end extends through the sealed agitator opening).

(431) In the illustrated implementation, the agitator **5028** includes a plurality of impellers **5029**. As shown in FIG. **43**, the impellers **5029** are attached to the drive shaft and spaced along the drive shaft's length. For example, in various implementations, the impellers **5029** may be positioned along the length of the drive shaft in order to provide sufficient agitation throughout the liquid plastic bath within the reactor vessel **5010**. Furthermore, each impeller **5029** may comprise one or more impeller blades (e.g., four impeller blades). In certain implementations, the impeller blades may be configured to extend radially outwardly from the drive shaft.

(432) As noted above, various implementations of the agitator **5028** are configured for continuously rotating (i.e., stirring) such that the liquid plastic inside the reactor vessel is kept in continuous motion. In this way, the agitator **5028** is configured for producing liquid flow velocities inside the reactor vessel **5010** necessary for the liquid plastic bath to acquire sufficient heat for pyrolysis to occur and/or while also avoiding overheating at the heated surfaces. For example, the agitator **5028** continuously circulates the liquid plastic throughout the reactor vessel's internal volume **5018** such that the entire liquid bath is agitated (e.g., substantially none of the liquid bath is static). In doing so, the motion of the agitator **5028** fosters rapid heat transfer from the heating elements **5034** to the liquid plastic.

(433) In the illustrated implementation of FIG. **43**, the continuously stirred pyrolysis reactor **5000** further includes a plurality of reactor sensors **5030**. In various implementations, the reactor sensors **5030** may be configured for measuring dynamic properties of the liquid plastic bath within the reactor vessel **5010**, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production). For example, in various implementations, the reactor sensors

5030 may comprise thermocouples, pressure sensors, flow meters, and the like. In certain implementations, the reactor sensors **5030** may comprise instrumentation probes having thermocouples arranged vertically along the length of a respective instrumentation probe to measure the liquid plastic bath level with the reactor vessel **5010**. Additionally, one or more of the instrumentation probes may be configured for measuring reactor vapor pressure. In this way, feedstock input (e.g., from the extruder **400**) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic bath within the reactor **5000**.

(434) In various implementations, a plurality of continuously stirred pyrolysis reactors **5000** can also be provided for use in the production of wax, oil, gas, or combinations thereof. For example, in one implementation, three continuously stirred pyrolysis reactors **5000** are used and can be operational in any combination with one another (e.g., such that all three pyrolysis reactors **5000** are processing feedstock simultaneously, or such that two of the pyrolysis reactors **5000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance). Additionally, in various implementations, the multiple pyrolysis reactors **5000** may be connected to a common manifold to direct vapor flow resulting from the pyrolysis process in each reactor.

(435) FIG. **45** shows another implementation of the continuously stirred pyrolysis reactor **5000** (like numbers refer to like elements throughout the figures). FIG. **46** provides a top view of the continuously stirred pyrolysis reactor **5000** shown in FIG. **45**. Certain elements depicted in FIG. **45** are also depicted in FIG. **46** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(436) In the illustrated implementation of FIG. **45**, the continuously stirred pyrolysis reactor **5000** includes a combination of gas-powered heating elements **5034** and electrically powered heating elements **5032**. In the illustrated implementation, the gas-powered heating elements **5034** are positioned laterally on the sides of the reactor vessel's cylindrical body **5012**. Furthermore, in the illustrated implementation, the internal heating elements **5032** comprise electric heaters (e.g., electric heating elements positioned within drywells) disposed such that they extend inwardly into the reactor vessel's internal volume **5018**. For example, in the illustrated embodiment of FIG. **45**, the internal heating elements **5032** extend laterally into the reactor vessel's internal volume **5018** from the sides of the reactor vessel **5010**. When activated, the transfer of heat from the electric heaters **5034** to the liquid plastic path (as well as the transfer of heat from the gas-powered heaters **5034** through the reactor vessel's cylindrical body **5012**) heats the internal volume **5018** of the reactor vessel **5010**.

(437) FIG. **47** shows another implementation of the continuously stirred pyrolysis reactor **5000** (like numbers refer to like elements throughout the figures). FIG. **48** provides a top view of the continuously stirred pyrolysis reactor **5000** shown in FIG. **47**. Certain elements depicted in FIG. **47** are also depicted in FIG. **48** and, accordingly, reference to either figure may be regarded as a reference to both figures.

(438) In the illustrated implementation of FIG. **47**, the continuously stirred pyrolysis reactor **5000** includes an extruder inlet pipe **5020** having an inlet opening (positioned outside of the reactor vessel **5010**) through which semi-molten feedstock may enter the extruder inlet pipe **5020**. The extruder inlet pipe **5020** extends into the reactor's internal volume **5018** and includes an outlet opening positioned at a height below the inlet opening. In the illustrated implementation, the extruder inlet pipe **5020** is mounted to the interior of the cylindrical body **5012** by an inlet pipe brace. As will be appreciated from FIG. **47**, when semi-molten feedstock is directed into the extruder inlet pipe **5020** via the inlet opening **5022**, the semi-molten feedstock will be directed through the extruder inlet pipe **5020** and deposited into the reactor vessel's internal volume **5018** for processing.

(439) In the illustrated implementation of FIG. **47**, the reactor **5000** includes a plurality of internal electric heaters **5033** disposed within the reactor vessel **5010** and a plurality of external electric

heaters **5035** disposed around the sidewalls of the reactor's cylindrical body **5012**. The internal electric heaters **5033** may comprise, for example, one or more heating elements disposed within dry wells. As shown in FIG. **47**, the internal electric heaters **5033** are vertically oriented and extend from the reactor vessel's upper ellipsoidal head **5014** and into the reactor's internal volume **5019**. For example, in the illustrated implementation the internal electric heaters **5033** each define a longitudinal axis that is parallel to the longitudinal axis of the reactor vessel's cylindrical body **5012**. In addition, each of the internal electric heaters **5033** extends into the reactor vessel's internal volume **5018** to a depth sufficient to allow energy transfer throughout the liquid plastic bath.

(440) In various implementations, the electric heaters **5033**, **5035** are generally configured to provide the heat needed to raise temperatures inside the pyrolysis reactor **5000** to a point where the depolymerization takes place. As described herein, the temperature of the electric heaters **5033**, **5035** is controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the liquid feedstock bath. Furthermore, the pyrolysis reaction within the reactor vessel **5010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.). In combination with continuous stirring of the liquid bath (e.g., via the agitator **5028**), the pyrolysis reaction within the reactor **5000** can be driven without producing conditions that promote char formation. Furthermore, as the electric heaters **5033**, **5035** are powered by electricity, various implementations of the pyrolysis reactor **5000** are configured for driving the pyrolysis process using only electricity (e.g., without using gas as a direct heat source).

(441) In the illustrated implementation, a plurality of internal electric heaters **5033** are provided within the reactor vessel **5010** and are arranged in a spaced-apart relationship within the reactor vessel **5010**. For example, in various implementations, numerous internal electric heaters **5033** may be used (e.g., two, three, four, five, six, seven, eight, nine ten, eleven, twelve, thirteen, fourteen, or fifteen or more internal electrical heaters **5033**). For example, the number of internal electric heaters within the reactor **5000** can be selected based on the size of the reactor and/or the size and power of the heaters. As shown in FIG. **48**, the internal electric heaters **5033** are arranged in an array within the reactor **5000** (e.g., a circular or semi-circular array). Additionally, in various implementations, the internal electric heaters **5033** may be substantially evenly spaced around the internal volume **5018** of the reactor vessel **5010**. By distributing the internal electric heaters **5033** throughout the internal volume **5018** in this way, the reactor **5000** can precisely control and evenly distribute heat input into the liquid feedstock bath.

(442) Referring back to FIG. **47**, in the illustrated embodiment, the agitator **5028** further includes a distal impeller **5027**. As shown in FIG. **47**, the agitator's distal impeller **5027** is positioned at a distal end of the agitator drive shaft **5042**. In the illustrated implementation, the distal impeller **5027** comprises an end plate and plurality of upwardly extending fins.

(443) By providing precise temperature control of the electric heaters **5033**, **5035** and minimizing the residence time of the liquid plastic against heated surfaces using the agitator **5028**, the reactor **5000** provides improved control of the heat input to the liquid plastic bath. In particular, the reactor **5000** offers more precise control over the liquid bath temperature in comparison to gas heater reactors. For example, in various implementations, the reactor **5000** is configured for maintaining the temperature of the liquid plastic within the reactor vessel **5010** at a temperature within 15° C. of a set point.

(444) As a result of its precise control over heat input and the liquid plastic temperature, the reactor **5000** can heat the liquid plastic to sufficient temperatures for depolymerization without causing localized overheating of the liquid plastic. In this way, the reactor **5000** avoids charring during the pyrolysis process. The reactor's ability to provide more precise heat application and temperature maintenance—thereby avoiding (or reducing) charring—can improve the overall efficiency of the production process for wax, oil, gas, or combinations thereof. Moreover, as a result of the reactor's improved temperature precision, higher average temperatures may be maintained in the liquid plastic (without causing charring or with minimal charring) and thereby increase overall throughput

in the reactor **5000**.

(445) FIG. **49** shows a side view of a molten material reactor **6000** according to one implementation. The molten material reactor **6000** is generally configured for pyrolyzing feedstock (e.g., semi-molten feedstock received from an extruder). Accordingly, the molten material reactor **6000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof. In other implementations, the molten material reactor **6000** is configured for receiving and pyrolyzing solid or semi-solid plastic feedstock (e.g., loose film, baled film, rigids, thermoforms, sheets, foams, non-wovens, strips, pellets, powder, purge patties, densified, shredded, and other post-consumer and/or post-industrial plastics). Accordingly, the molten material reactor **6000** can be used in the methods described herein for producing hydrocarbon-based compositions derived from pyrolysis of feedstock comprising post-consumer and/or post-industrial plastics, including wax, oil, gas, or combinations thereof.

(446) As shown in FIG. **49**, the molten material reactor **6000** includes a reactor vessel **6010** within which plastic feedstock is deposited and pyrolyzed. The reactor vessel **6010** can be a vessel of any suitable geometry or shape for containing a molten material **6015** and plastic feedstock. The reactor vessel can, for example, comprise a cylindrical body **6012** extending between a first end **6006** and a second end **6008**. Together, the cylindrical body **6012**, first end **6006** and second end **6008** define an internal volume **6018**. In various implementations, the cylindrical body **6012**, first end **6006**, and second end **6008** may be constructed from stainless steel (or other materials with suitable structural and thermal properties). As shown in FIG. **49**, the reactor vessel **6010** may be mounted in a substantially horizontal position (e.g., such that its longitudinal axis is substantially horizontal).

(447) The molten material reactor **6000** further comprises a feedstock inlet **6020**, a material inlet **6021**, a discharge manifold **6022**, a vapor outlet **6024**, a plurality of reactor sensors **6030**, one or more external heating elements **6034**, and a product collection system **6036**. Semi-molten feedstock (e.g., received from an extruder) is deposited into the reactor vessel's internal volume **6018** by way of the feedstock inlet **6020**. In various implementations, the feedstock inlet **6020** defines an external opening and extends into the reactor vessel **6010**. In the illustrated implementation, the plastic feedstock (e.g., semi-molten feedstock received from an extruder) is deposited into the reactor vessel's internal volume **6018** by way of the feedstock inlet **6020**. In various implementations, the feedstock inlet's external inlet opening is positioned outside of the reactor vessel **6010** and defines an aperture through which plastic feedstock may enter the feedstock inlet **6020**. The feedstock inlet **6020**, which may comprise, for example, a pipe, extends into the internal volume **6018** and includes an outlet opening positioned within the reactor vessel's internal volume **6018**. As will be appreciated from FIG. **49**, when plastic feedstock (e.g., semi-molten feedstock) is directed through the feedstock inlet **6020** via its inlet opening, the plastic feedstock will be directed through feedstock inlet and deposited within the reactor vessel's internal volume **6018** for processing.

(448) The material utilized for heat transfer in the molten material reactor **6000** is deposited into the reactor vessel's internal volume **6018** by way of the material inlet **6021**. In various implementations, the material inlet **6021** is positioned substantially below the feedstock inlet **6020** at the first end **6006** of the reactor vessel **6010**. In various implementations, the material inlet **6021** defines includes an external inlet opening positioned outside of the reactor vessel **6010** and defines an aperture through which material may enter the material inlet **6021**. The material inlet **6021**, which may comprise, for example, a pipe, extends into the internal volume **6018** and includes an outlet opening positioned within the reactor vessel's internal volume **6018**. As will be appreciated from FIG. **49**, when the material (e.g., a metal or salt) is directed through the material inlet **6021** via its inlet opening, the plastic feedstock will be directed through feedstock inlet and deposited within the reactor vessel's internal volume **6018** for processing.

(449) As shown in FIG. **49**, the molten material reactor **6000** can include at least one heating

element **6034** configured for heating the internal volume **6018** of the reactor vessel **6010**. In some implementations, the heating elements **6034** can comprise both electric heaters (positioned externally around the sides of the reactor vessel's cylindrical body **6012**) and gas heaters (positioned beneath or around the reactor vessel's cylindrical body **6012**). In one implementation, as shown in FIG. **49**, the heating element **6034** comprises an external gas heater positioned beneath the reactor vessel's cylindrical body **6012**. When activated, the transfer of heat from the heating elements **6034** through the reactor vessel's cylindrical body **6012** thereby heats the internal volume **6018** of the reactor vessel **6010**. In other implementations, the heating elements **6034** may comprise all electric or all electric heating elements and may be positioned internally or externally to the reactor vessel **6010**.

(450) In various implementations, the heating elements **6034** are generally configured to provide the heat needed to raise temperatures inside the reactor vessel **6010** to a point where depolymerization takes place. In the molten material reactor **6000**, a material, such as a metal (e.g., zinc) or a salt, is heated by the heating element(s) **6034**. As a result, when plastic feedstock is directed through the feedstock inlet **6020** into the internal volume **6018**, pyrolysis is facilitated through the plastic feedstock's contact directly with the molten material **6015**. As a result, the molten material **6015** transfers heat directly to the liquid plastic feedstock within the reactor vessel **6010**. The heating elements **6034** may be controlled to provide a prescribed temperature and heat density (W/in.sup.2) that results in a controlled heat flux into the mixture of liquid feedstock bath and molten material **6015** within the reactor vessel **6010**. In particular, the pyrolysis reaction within the reactor vessel **6010** can be controlled to provide a desired reaction temperature and energy density (kW/lb.).

(451) The molten material reactor **6000** can further include a discharge manifold **6022**. In various implementations, the discharge manifold **6022** is configured to provide an outlet for material within the reactor vessel **6010**. For example, the discharge manifold **6022** may be used to transfer or otherwise remove liquid plastic (or other material generated during the pyrolysis process) or molten material **6015** from the reactor vessel **6010**. Accordingly, various implementations of the discharge manifold **6022** may include a sealable discharge opening (e.g., a port which can be selectively opened or sealed and closed).

(452) As shown in FIG. **49**, the molten material reactor **6000** also includes a vapor outlet **6024**. In various implementations, the vapor outlet **6024** defines an internal opening (positioned within the reactor vessel's internal volume **6018**) and an external opening (positioned outside of the reactor vessel **6010**). The vapor outlet **6024**, which may comprise, for example, a pipe, extends into the reactor vessel **6010** through the reactor vessel's cylindrical body **6012** and enables vapor produced during pyrolysis of the plastic feedstock within the reactor vessel **6010** to exit the reactor vessel **6010**.

(453) As noted above, during the pyrolysis process, the hydrocarbon plastic chains and groups of rings within the liquid plastic are split apart by the heating process into smaller segments until they are small and light enough to vaporize and exit the reactor as a vapor.

(454) Accordingly, the reactor's vapor outlet **6024** is configured to provide a conduit for hydrocarbon vapor exiting the reactor **6000** and thus extends upwardly from the reactor vessel **6010**. In various implementations, the vapor outlet **6024** may be connected (e.g., via additional piping or a ducting manifold) to a product recovery system. For example, in the illustrated implementation of FIG. **49**, the vapor outlet **6024** is configured to direct vapor exiting the reactor vessel **6010** following pyrolysis to a product collection system **6036** configured for product recovery (e.g., production of wax, oil, gas, or combinations thereof as described herein).

(455) In the illustrated implementation of FIG. **49**, the molten material reactor **6000** further includes a plurality of reactor sensors **6030**. The reactor sensors **6030** can be disposed in various locations throughout the reactor vessel **6010**. In various implementations, the reactor sensors **6030** may be configured for measuring dynamic properties of the liquid plastic bath within the reactor

vessel **6010**, the molten material **6015**, as well as the dynamic properties of the reactor's input (e.g., feedstock input) and output (e.g., vapor production). For example, in various implementations, the reactor sensors **6030** may comprise thermocouples, pressure sensors, flow meters, and the like. In this way, feedstock input (e.g., from the extruder **400**) and product output can be monitored and/or adjusted based on the observed variations in the liquid plastic bath within the reactor **6000**.

(456) In various implementations, a plurality of molten material reactors **6000** can also be provided for use in the production process wax, oil, gas, or combinations thereof. For example, in one implementation, three molten material reactors **6000** are used and can be operational in any combination with one another (e.g., such that all three molten material reactors **6000** are processing feedstock simultaneously, or such that two of the molten material reactors **6000** are processing feedstock while a third remains on standby in the event one of the other reactors requires service or maintenance).

(457) Vaporized Product Recovery

(458) Vapor leaving the reactors contains a complex hydrocarbon mixture ranging from light molecules (short carbon chains) to heavy molecules (long carbon chains). The process uses a production collection system comprising, for example, one or more stages of cooling and condensation to condense the vapor product into one or more liquid products. In some examples, the vapor can be subjected to an additional processing step (e.g., further heated, distilled, filtered, etc.) before and/or after condensation.

(459) For example, vapor from the reactors enters a condenser where hydrocarbons that have a boiling point at or above the temperature of the condenser are condensed. The condenser can comprise any suitable condenser. Condensed liquid from the condenser can then be transferred, for example, to a storage tank. In some examples, condensed liquid from the condenser can then be distilled, for example to separate the product into one or more fractions and/or purify the product.

(460) In some examples, the process uses a plurality of stages of cooling and condensation to selectively separate reactor vapor product into a wax product (e.g., comprising long-chain hydrocarbons that are a solid or semi-solid wax at ambient temperatures) and an oil product (e.g., comprising lighter, shorter-chain hydrocarbons that are a liquid at ambient temperatures). In some examples, there is also uncondensed gas.

(461) In some examples, wax condensation takes place inside a first condenser (e.g., a wax condenser). The first condenser can comprise any suitable condenser. For example, vapor from the reactors enters the first condenser where hydrocarbons that have a boiling point at or above the temperature of the first condenser are condensed. Condensed liquid (e.g., liquid wax) from the first condenser can then be transferred, for example, to a storage tank (e.g., a wax storage tank).

(462) In some examples, vapor phase material that passes through the wax condenser can flow to a second condensing system (e.g., a second condenser). The second condenser can comprise any suitable condenser. For example, vapor from the wax condenser enters the second condenser where hydrocarbons that have a boiling point at or above the temperature of the second condenser are condensed. Condensed liquid (e.g., liquid oil) from the second condenser can then be transferred, for example, to a storage tank (e.g., an oil storage tank).

(463) In some examples, vapor phase material that passes through the second condenser, such as uncondensed hydrocarbons (e.g., pentanes and some heavier, longer chain alkanes) and non-condensables (e.g., butane and lighter hydrocarbons and any non-hydrocarbon gases), can flow to a gas-liquid separator and/or to a third condenser. The gas-liquid separator, when present, can comprise any suitable separator.

(464) In some examples, vapor phase material that passes through the second condenser can flow to a third condenser. The third condenser can comprise any suitable condenser. For example, vapor from the second condenser enters to the third condenser where hydrocarbons that have a boiling point at or above the temperature of the third condenser are condensed, such as C.sub.5-C.sub.7 hydrocarbons. Condensed liquid from the third condenser can then be transferred, for example, to a

storage tank.

(465) In various implementations, numerous condensers may be used as part of the product recovery collection system (e.g., 2, 3, 4, 5, 6, 7, 8, 9, 10 or more condensers).

(466) In some examples, the temperature cut-off of each of the one or more condensers can be selected in view of a variety of factors. In some examples, the temperature cut-off of the one or more condensers can be selected such that a portion of the oil product is not condensed. For example, a certain portion of the oil product can, in some examples, comprise a high concentration of contaminants, and the condensers can be configured to selectively allow this portion of the oil product to pass through each of the one or more condensers without condensing.

(467) In some examples, the systems and/or methods described herein can produce the pyrolysis products (e.g., wax and/or oil) at a yield of 50% or more (e.g., 51% or more, 52% or more, 53% or more, 54% or more, 55% or more, 56% or more, 57% or more, 58% or more, 59% or more, 60% or more, 61% or more, 62% or more, 63% or more, 64% or more, 65% or more, 66% or more, 67% or more, 68% or more, 69% or more, 70% or more, 71% or more, 72% or more, 73% or more, 74% or more, 75% or more, 76% or more, 77% or more, 78% or more, 79% or more, 80% or more, 81% or more, 82% or more, 83% or more, 84% or more, 85% or more, 86% or more, 87% or more, 88% or more, 89% or more, 90% or more, 91% or more, 92% or more, 93% or more, 94% or more, 95% or more, 96% or more, 97% or more, 98% or more, or 99% or more). In some examples, the systems and/or methods described herein can produce the pyrolysis products (e.g., wax and/or oil) at a yield of 100% or less (e.g., 99% or less, 98% or less, 97% or less, 96% or less, 95% or less, 94% or less, 93% or less, 92% or less, 91% or less, 90% or less, 89% or less, 88% or less, 87% or less, 86% or less, 85% or less, 84% or less, 83% or less, 82% or less, 81% or less, 80% or less, 79% or less, 78% or less, 77% or less, 76% or less, 75% or less, 74% or less, 73% or less, 72% or less, 71% or less, 70% or less, 69% or less, 68% or less, 67% or less, 66% or less, 65% or less, 64% or less, 63% or less, 62% or less, 61% or less, 60% or less, 59% or less, 58% or less, 57% or less, 56% or less, 55% or less, 54% or less, 53% or less, or 52% or less).

(468) The yield of the systems and/or methods described herein can range from any of the minimum values described above to any of the maximum values described above. For example, the systems and/or methods described herein can produce the pyrolysis products (e.g., wax and/or oil) at a yield of from 50% to 100% (e.g., from 50% to 75%, from 75% to 100%, from 50% to 60%, from 60% to 70%, from 70% to 80%, from 80% to 90%, from 90% to 100%, from 50% to 95%, from 50% to 90%, from 50% to 85%, from 50% to 80%, from 50% to 70%, from 50% to 65%, from 50% to 55%, from 55% to 100%, from 60% to 100%, from 65% to 100%, from 70% to 100%, from 80% to 100%, from 85% to 100%, from 90% to 100%, from 55% to 95%, or from 80% to 95%).

(469) Post-Treatment

(470) In some examples, the methods and systems herein produce a raw pyrolysis product with a reduced level of contaminants, for example such that no further post-treatment of the product is needed (e.g., the methods substantially exclude any hydrotreatment or further refining steps after the pyrolysis).

(471) In some examples, the methods and systems herein can further comprise post-treating the pyrolysis products. For example, the wax and/or oil can be further processed by refining, filtering, cracking, hydrotreating, distilling, etc., or a combination thereof. In some examples, the post-treatment can reduce the level of one or more contaminants in the pyrolysis product (e.g., oil and/or wax).

(472) Product Storage

(473) After hydrocarbon product has been condensed as wax (molten) and/or oil (and optionally post-treated), it is transferred to storage tanks. Liquid product can be transferred using any suitable means to the storage tanks.

(474) The storage tanks can be constructed of any suitable material. In some examples, the storage

tanks can further include a feedback system. For example, liquid levels in the tanks can be monitored using an electronic sensor. In some examples, the feedback system can include a temperature control system (e.g., to control the temperature of the liquid within the storage tank, for example by heating and/or cooling). The feedback system can, for example, activate the heating and/or cooling systems as needed, for example based on particular temperature set-points. In some examples, at least a portion of the storage tank(s) can be insulated.

(475) Heat Tracing

(476) In some examples, the system can further include heat trace components. For example, mineral insulated heat trace cable can be used on some or all process lines conveying either molten plastic or liquid products. This cable can ensure that products within the process lines remain flowable under all conditions. Such cables can be protected through cladded insulation.

Thermocouples on each independent section of heat trace can be installed to monitor heat levels within these sections and feedback mechanisms can provide an alert if piping sections may not be receiving proper heating. For example, some or all of the piping running from the extruder into the reactors can be insulated and/or include heat tracing. Such insulating and heat tracing to process lines can be particularly important during colder ambient conditions. It is imperative that all process lines always remain fully open and operable, regardless of the ambient temperature.

(477) System Availability

(478) System availability is typically expressed as a percentage and refers to the amount of time a system is operating, divided by the total amount of time in the period. Availability is a combination of scheduled maintenance (non-operating hours) and reliability (defined as 1 minus forced outages divided by operating hours). Availability is dependent on several factors, including the quality of equipment, engineering and construction employed, the degree of back-up or redundant equipment, the expertise and effort of personnel, the level of preventative, predictive and corrective maintenance, the replenishment of spare parts, the operating demand placed on a facility, and first year versus mature operation.

(479) In some examples, the systems and methods described herein can have an availability factor of 50% or more (e.g., 55% or more, 60% or more, 65% or more, 70% or more, 75% or more, 80% or more, 85% or more, 90% or more, or 95% or more). In some examples, the systems and methods described herein can have an availability factor of 100% or less (e.g., 95% or less, 90% or less, 85% or less, 80% or less, 75% or less, 70% or less, 65% or less, or 60% or less). The availability factor can range from any of the minimum values described above to any of the maximum values described above. For example, the systems and methods described herein can have an availability factor of from 50% to 100% (e.g., from 50% to 75%, from 75% to 100%, from 50% to 60%, from 60% to 70%, from 70% to 80%, from 80% to 90%, from 90% to 100%, from 50% to 80%, from 50% to 70%, from 60% to 100%, from 70% to 100%, from 80% to 100%, from 90% to 100%, from 95% to 100%, from 55% to 95%, or from 60% to 90%).

(480) Compositions, Articles of Manufacture, Methods of Use

(481) Also disclosed herein are compositions comprising any of the waxes disclosed herein, any of the oils disclosed herein, any of the blends disclosed herein, or any of the products of the methods or systems disclosed herein.

(482) Also disclosed herein are compositions derived from any of the waxes disclosed herein, any of the oils disclosed herein, any of the blends disclosed herein, or any of the products of the methods or systems disclosed herein.

(483) Also disclosed herein are methods of using any of the compositions described herein (e.g., any of the waxes disclosed herein, any of the oils disclosed herein, any of the blends disclosed herein, or any of the products of the methods or systems disclosed herein).

(484) Also disclosed herein are articles of manufacture comprising any of the compositions described herein (e.g., any of the waxes disclosed herein, any of the oils disclosed herein, any of the blends disclosed herein, or any of the products of the methods or systems disclosed herein).

(485) Also disclosed herein are methods of making any of the compositions or articles of manufacture, for example, wherein the method comprises additional processing of the composition, such as refining, filtering, cracking, hydrotreating, etc.

(486) In some examples, the composition or article comprises a lubricating oil, a mineral oil, a group III base oil, a fully refined paraffin wax, or a combination thereof.

(487) In some examples, the composition or article comprises a binder, a processing aid, or a combination thereof.

(488) In some examples, the composition or article comprises kerosene including cosmetic kerosene, white oils, high value paraffin and purified liquid fuels, or a combination thereof.

(489) In some examples, the composition or article comprises naphtha.

(490) In some examples, the composition or article comprises fuel.

(491) In some examples, the composition or article comprises liquefied petroleum gas (LPG), naphtha, kerosene, diesel and gas oil, or a combination thereof.

(492) In some examples, the composition or article comprises lube oil, gasoline, jet fuel, diesel fuel, or a combination thereof.

(493) In some examples, the composition or article comprises packaging, film, and/or fibers for carpets and clothing, molded articles, and extruded pipes, or a combination thereof.

(494) In some examples, the composition or article comprises a medical device.

(495) In some examples, the composition or the article comprises lubricant, candles, adhesives, packaging, rubber, cosmetics, fire logs, bituminous mixtures, superficial wear coatings, asphalt, sealing coatings, or a combination thereof.

(496) In some examples, the composition or article comprises asphalt, automotive fuel, aviation fuels, base oil, bitumen, cadalene, cutting fluid, diesel fuel, fuel oil, gasoline, heating oil, heavy fuel oil, hydrocarbon solvents, jet fuel, kerosene, ligroin, lubricant, mazut, microcrystalline wax, mineral oil, motor fuel, motor oil, naphtha, naphthenic acid, paraffin wax, petroleum benzene, petroleum ether, petroleum jelly, petroleum naphtha, petroleum resin, retene, or a combination thereof.

(497) In some examples, the composition or article comprises gasoline, jet fuel, diesel and other fuels, asphalt, heavy fuel oil, lubricants, paraffin wax, tar, asphalt, fertilizer, flooring, perfume, insecticide, petroleum jelly, soap, vitamin, amino acid, or a combination thereof.

(498) In some examples, the composition or article comprises wood-based composites such as oriented-strand board (OSB), particleboard, hardboard, medium density fiberboard, gypsum board, or a combination thereof.

(499) In some examples, the composition or article comprises fully refined paraffin which is used to produce candles, cosmetics, crayons, food packaging, paper and carton coatings, or a combination thereof.

(500) In some examples, the composition or article comprises a hydrocarbon feedstock for a petroleum refinery, a catalytic cracking system, a thermal cracking system, a polymerization system, or a combination thereof. For example, also disclosed herein are methods of using any of the compositions disclosed herein as a hydrocarbon feedstock for a petroleum refinery, a catalytic cracking system, a thermal cracking system, a polymerization system, or a combination thereof.

(501) A number of embodiments of the invention have been described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention. Accordingly, other embodiments are within the scope of the following claims.

(502) The examples below are intended to further illustrate certain aspects of the systems and methods described herein, and are not intended to limit the scope of the claims.

EXAMPLES

(503) The following examples are set forth below to illustrate the methods and results according to the disclosed subject matter. These examples are not intended to be inclusive of all aspects of the subject matter disclosed herein, but rather to illustrate representative methods and results. These

examples are not intended to exclude equivalents and variations of the present invention which are apparent to one skilled in the art.

(504) Efforts have been made to ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.) but some errors and deviations should be accounted for. Unless indicated otherwise, parts are parts by weight, temperature is in ° C. or is at ambient temperature, and pressure is at or near atmospheric. There are numerous variations and combinations of measurement conditions, e.g., component concentrations, temperatures, pressures and other measurement ranges and conditions that can be used to optimize the described process.

Example 1

(505) A wax derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics was produced and analyzed. At ambient temperature and pressure, the wax was a solid with an amber to beige color.

(506) The following techniques were applied to the wax: UV-Vis, FTIR, carbon number distribution by GC, hydrocarbon types by clay-gel absorption chromatography, ¹H-NMR, and ¹³C-NMR.

(507) A summary of the substance identity profile is provided in Table 1.

(508) TABLE-US-00001 TABLE 1 Summary of wax product. Concentration Hydrocarbon type (% w/w) Saturated content 97.9 Unsaturated content 1.0 Aromatic content 1.1 Asphaltene content <0.1 Hydrocarbon Concentration number (% w/w) C9 0.59 C10 0.40 C11 0.75 C12 0.87 C13 1.27 C14 1.78 C15 1.94 C16 2.39 C17 3.07 C18 3.78 C19 4.15 C20 5.06 C20-C24 22.80 C24-C28 22.10 C28-C32 14.91 C32-C36 7.75 C36-C40 3.63 C40-C44 1.49 C44-C46 0.39 C46+ 0.88

(509) UV-Vis spectrophotometry was performed using a Shimadzu UV1800 spectrophotometer using a single cell (10 mm) over a wavelength range of from 200 to 800 nm. The sample was dispersed in hexane (dilution factor 100 and 100×). The UV-Vis results (FIG. 6 and FIG. 7) show that the sample had maximum absorptions at wavelengths of 380 nm, 325 nm, 255 nm, and 200 nm.

(510) FTIR-ATR spectroscopy was performed using a Perkin Elmer Instruments Spectrum Three FT-IR Spectrometer, equipped with an ATR Golden Gate bridge (crystal=diamond) over a spectral range of 4,000 to 600 cm.^{sup.}−1 with baseline correction. The FTIR spectrum is shown in FIG. 7. The FTIR main peaks are summarized in Table 2.

(511) TABLE-US-00002 TABLE 2 FTIR main peaks of wax product. Main FTIR-ATR Peaks (cm.^{sup.}−1) Interpretation 2955 Anti-symmetric stretching of methyl 2916 Anti-symmetric stretching of methylene 2871 Symmetric stretching of methyl 2848 Symmetric stretching of methylene 1472/1463 Anti-symmetric bending vibrations of methyl and methylene 1378 Umbrella bending vibrations of methyl 965 C—C skeleton vibrations, methyl bending 729/719 Methylene bending rocking vibrations (crystallinity)

(512) Carbon number distribution in the wax product was assessed by simulated distillation (GC) using ASTM D5442M and ASTM D2887. The GC chromatogram of the wax product is shown in FIG. 9. The results are summarized in Table 3-Table 5.

(513) TABLE-US-00003 TABLE 3 Carbon number distribution parameters. TEST RESULT UNITS Initial Boiling Point 148.2 ° C. Final Boiling Point (@ 99.5%) 571.0 BOILING % OFF POINT UNITS 0.5 148.2 ° C. 5.0 251.3 ° C. 10.0 287.0 ° C. 15.0 307.5 ° C. 20.0 325.2 ° C. 25.0 340.0 ° C. 30.0 352.2 ° C. 35.0 363.1 ° C. 40.0 373.1 ° C. 45.0 383.3 ° C. 50.0 393.1 ° C. 55.0 401.9 ° C. 60.0 410.4 ° C. 65.0 419.3 ° C. 70.0 428.7 ° C. 75.0 438.8 ° C. 80.0 450.5 ° C. 85.0 462.6 ° C. 90.0 479.0 ° C. 95.0 503.2 ° C. 99.5 571.0 ° C.

(514) TABLE-US-00004 TABLE 4 ASTM D86 correlation results. BOILING % OFF POINT UNITS IBP 239.9 ° C. 5.0 291.9 ° C. 10.0 310.5 ° C. 20.0 334.7 ° C. 30.0 355.9 ° C. 40.0 — ° C. 50.0 383.5 ° C. 60.0 — ° C. 70.0 414.3 ° C. 80.0 428.1 ° C. 90.0 451.3 ° C. 95.0 471.3 ° C. FBP 484.3 ° C. % vol at 350° C.

(515) TABLE-US-00005 TABLE 5 Cut points. CARBON BP NUMBER (° C.) % OFF C9 151

0.5907 C10 174 0.9886 C11 196 1.7416 C12 216 2.6140 C13 235 3.8843 C14 254 5.6676 C15 271 7.6124 C16 287 10.0047 C17 302 13.0783 C18 316 16.8539 C19 330 21.0007 C20 344 26.0614 C24 391 48.8578 C28 431 70.9595 C32 466 85.8719 C36 496 93.6182 C40 522 97.2452 C44 545 98.7369 C46 556 99.1241

(516) Hydrocarbon types in the wax sample were further assessed using clay-gel absorption chromatography according to ASTM D2007. The results are summarized in Table 6.

(517) TABLE-US-00006 TABLE 6 ASTM D2007 results. Hydrocarbon Result Units Saturate content 86.1 Wt % Aromatic content 12.8 Wt % Polar content 1.1 Wt % Asphaltenes <0.1 Wt %

(518) The wax sample was further subjected to ¹H-NMR spectroscopy. The ¹H spectra were obtained in CDCl₃ solvent (Goss Scientific D, 99.8%) at ambient laboratory temperature and auto referenced against the solvent peak using the JEOL ECS 400 NMR spectrometer.

(519) The ¹H-NMR spectra are shown in FIG. 11 and FIG. 12. The annotations in FIG. 12 is a guide highlighting certain peaks of interest. The ¹H-NMR spectra generated for the wax sample are dominated by resonances that are consistent with saturated, unsaturated and aromatic hydrocarbons.

(520) The normalized NMR integration values indicate there is 97.9% aliphatic protons (region 0.5-3.2 ppm), 1.0% unsaturated protons (region 4.5-6.0 ppm) and 1.1% aromatic protons (region 6.5-8.5 ppm). This refers to the percentage of proton atoms in the aliphatic saturated, unsaturated and aromatic rings only relative to the total proton content. There were no signals observable outside the range shown in the ¹H-NMR spectra.

(521) The wax sample was further subjected to ¹³C-NMR spectroscopy. The ¹³C-NMR spectra were obtained in CDCl₃ solvent (Goss Scientific D, 99.8%) at ambient laboratory temperature and auto referenced against the solvent peak.

(522) The ¹³C-NMR spectra are shown in FIG. 13 and FIG. 14. The annotations in FIG. 14 is a guide highlighting certain peaks of interest. The ¹³C-NMR spectra generated for the wax sample are dominated by resonances that are consistent with saturated, unsaturated and aromatic hydrocarbons. There were no signals observable outside the range shown in the ¹³C-NMR spectra.

Example 2

(523) An oil derived from pyrolysis of a feedstock comprising post-consumer and/or post-industrial plastics was produced and analyzed. At ambient temperature and pressure, the oil was a dark brown, clear liquid.

(524) The following techniques were applied to the wax: UV-Vis, FTIR, GC-FID, GC-MS, kinematic viscosity, flash point, distillation characteristics, ¹H-NMR, and ¹³C-NMR.

(525) A summary of the substance identity profile is provided in Table 7.

(526) TABLE-US-00007 TABLE 7 Summary of oil product. Concentration Hydrocarbon types (% w/w) Aliphatic content 94.8 Unsaturated content 3.8 Aromatic content 1.4 Hydrocarbon Concentration number (% w/w) C2 0.03 C3 0.61 C4 1.64 C5 6.62 C6 9.03 C7 5.47 C8 8.68 C9 14.1 C10 6.34 C11 7.69 C12 5.30 C13 5.14 C14 6.19 C15 4.32 C16 3.51 C17 3.09 C18 2.82 C19 2.21 C20 1.63 C21 1.22 C22 0.86 C23 0.64 C24 0.85 C25 0.70 C26 0.58 C27 0.42 C28 0.24 C29 0.13

(527) UV-Vis spectrophotometry was performed using a Shimadzu UV1800 spectrophotometer using a single cell (10 mm) over a wavelength range of from 200 to 800 nm. The sample was dispersed in hexane (dilution factor 100 and 100×). The UV-Vis results (FIG. 15 and FIG. 16) show that the sample had maximum absorptions at wavelengths of 335 nm, 245 nm, and 200 nm.

(528) FTIR-ATR spectroscopy was performed using a Perkin Elmer Instruments Spectrum Three FT-IR Spectrometer, equipped with an ATR Golden Gate bridge (crystal=diamond) over a spectral range of 4,000 to 600 cm^{sup.}−1 with baseline correction. The FTIR spectrum is shown in FIG. 17. The FTIR main peaks are summarized in Table 8.

(529) TABLE-US-00008 TABLE 8 FTIR main peaks of oil product. Main FTIR-ATR Peaks

(cm.sup.-1) Interpretation 2956 Anti-symmetric stretching of methyl 2922 Anti-symmetric stretching of methylene 2853 Symmetric stretching of methylene 1457 Anti-symmetric bending vibrations of methylene 1378 Umbrella bending vibrations of methyl 992 Methyl bending 965 C—C skeleton vibrations, methyl bending 721 Methylene bending rocking vibrations (530) Gas chromatography was performed on the oil product using an Agilent 6890 Gas Chromatograph with Atlas software and a flame ionization detector (GC-FID) (GC temperature program: Initial 20° C.—10 minutes; Ramp 1.5° C./min to 250° C.; Final 250° C.—10 minutes). The GC spectra are shown in FIG. 18 and FIG. 19. The results are summarized in Table 9 and Table 10.

(531) TABLE-US-00009 TABLE 9 Extended PIONA results. Identified carbon chain length Area % C1 <0.01 C2 0.03 C3 0.61 C4 1.64 C5 6.62 C6 9.03 C7 5.47 C8 8.68 C9 14.1 C10 6.34 C11 7.69 C12 5.30 C13 5.14 C14 6.19 C15 4.32 C16 3.51 C17 3.09 C18 2.82 C19 2.21 C20 1.63 C21 1.22 C22 0.86 C24 0.85 C25 0.70 C26 0.58 C27 0.42 C28 0.24 C29 0.13 Total 100

(532) TABLE-US-00010 TABLE 10 Extended PIONA substance list. Substance Area % Substance Area % Pentane 3.95 Decane 2.82 Hexadecane 2.77 Hexane 2.14 Undecane 2.98 Heptadecane 2.44 Heptane 2.48 Dodecane 3.14 Octadecane 2.19 Octane 2.59 Tridecane 3.14 Nonadecane 1.79 3-ethylheptane 2.96 Tetradecane 3.12 Eicosane 1.45 Nonane 2.68 Pentadecane 2.91 Heneicosane 1.09

(533) Gas chromatography—Mass spectrometry (GC-MS) was performed using a Thermo Scientific Trace 1300 GC with a Thermo Scientific ISQ QD (injection volume—0.5 microliters; split ratio 1:5; injection temperature 250° C.; oven program—70° C., hold 1 min, 10° C./min to 300° C., hold 24 min). The GC-MS results are summarized in Table 11.

(534) TABLE-US-00011 TABLE 11 GC-MS results. Retention time (min) Component 1.57 Propane 1.61 Isobutane 1.63 1-butene 1.65 2-butene 1.73 Butane, 2-methyl- 1.77 Pentane 1.80 C5 alkene (m/z 55, 42, 41) 1.91 1-Pentene, 4-methyl- 1.94 Butane, 2,3-dimethyl- 2.01 Pentane, 2-methyl- 2.05 n-Hexane 2.08 C6 alkene (m/z 84, 41, 69) 2.12 C6 alkene (m/z 41, 55, 84) 2.15 C6 alkene (m/z 41, 67, 39) 2.18 Hexane, 2-methyl- 2.20 Cyclopentane, methyl- 2.28 1-Pentene, 2,4-dimethyl- 2.30 C7 alkene (m/z 83, 98, 41) 2.33 Cyclopentene, 1-methyl- 2.38 Hexane, 2-methyl- 2.40 Benzene 2.44 Hexane, 3-methyl- 2.54 C7 alkene (m/z 41, 98, 55) 2.61 Heptane 2.65 (m/z 98, 81, 96) 2.71 C7 alkene (m/z 98, 41, 39) 2.84 Cyclohexane, methyl- 2.92 Cyclopentane, ethyl- 2.98 C7H12 (m/z 81, 96, 79) 3.08 C7H12 (m/z 81, 96, 95) 3.19 Heptane, 4-methyl- 3.24 Toluene 3.28 C7H12 (m/z 96, 81, 91) 3.39 C8 alkene (m/z 41, 112, 55) 3.43 C8 alkene (m/z 41, 55, 43) 3.55 Octane 3.59 (m/z 112, 41, 55) 3.61 Dimethylcyclohexane 3.79 C9H20 alkane (m/z 85, 43, 41) 3.91 (m/z 83, 126, 41) 4.07 C9 alkene (m/z 43, 126, 55) 4.15 (m/z 110, 95, 109) 4.30 Cyclohexane, 1,3,5-trimethyl- 4.37 xylene (m/z 91, 106, 105) 4.47 xylene + (m/z 106, 91, 109) 4.57 C9H16 (m/z 109, 124, 83) 4.70 C9 alkene (m/z 41, 43, 97) 4.76 C10H20 (m/z 43, 83, 104) 4.82 xylene + (m/z 106, 43, 91) 4.84 Nonane 5.23 Benzene, (1-methylethyl)- 5.32 (m/z 97, 83, 126) 5.64 Benzene, propyl- 5.71 (m/z 124, 41, 95) 5.76 aromate C9H12 (m/z 105, 120, 103) 5.79 aromate C9H12 (m/z 105, 120, 106) 5.86 aromate C9H12 (m/z 105, 120, 119) 6.05 aromate C9H12 (m/z 105, 120, 103) 6.14 C10H20 alkene (m/z 41 97, 55) 6.29 Decane 6.35 C10H20 alkene (m/z 140, 97, 41) 6.43 (m/z 113, 43, 41) 6.50 C11H24 alkane (m/z 43, 113, 41) 6.79 (m/z 154, 41, 111) 6.97 Indane 7.13 aromate C10H14 (m/z 105, 134, 85) 7.24 (m/z 119, 43, 85) 7.32 (m/z 119, 105, 41) 7.48 (m/z 111, 112, 41) 7.55 (m/z 119, 111, 112) 7.68 (m/z 119, 41, 97) 7.76 aromate C10H12 (m/z 117, 115, 132) 7.86 Undecane 7.89 C11H22 alkene (m/z 154, 97, 41) 8.01 C11H22 alkene (m/z 154, 41, 152) 8.22 (m/z 152, 125, 41) 8.44 (m/z 154, 119, 152) 8.57 aromate (m/z 117, 152, 115) 8.61 (m/z 131, 119, 146) 8.67 aromate (m/z 148, 105, 106) 8.75 aromate (m/z 117, 115, 132) 8.83 aromate (m/z 148, 119, 115) 8.92 aromate (m/z 148, 105, 106) 9.17 C12 alkene (m/z 97, 168, 41) 9.29 (m/z 131, 170, 43) 9.32 Naphthalene 9.37 Dodecane 9.39 C12 alkene (m/z 168, 97, 131) 9.46 aromate C11H14 (m/z 131, 146, 115) 9.50 (m/z 168, 131, 146) 9.82 (m/z 145, 155, 160) 9.92

(m/z 162, 166, 155) 9.97 (m/z 168, 117, 183) 10.02 (m/z 162, 117, 119) 10.07 (m/z 145, 166, 160) 10.12 (m/z 145, 162, 160) 10.21 (m/z 131, 146, 162) 10.27 (m/z 162, 166, 91) 10.38 (m/z 162, 105, 145) 10.43 (m/z 131, 146, 145) 10.47 (m/z 146, 131, 144) 10.53 (m/z 144, 129, 145) 10.62 1-tridecene 10.82 Tridecene 10.84 (m/z 182, 197, 111) 10.89 (m/z 111, 43, 125) 10.98 (m/z 111, 141, 142) 11.09 (m/z 111, 154, 125) 11.23 Methylanthalene (m/z 142, 141, 115) 11.44 C13 alkene (m/z 182, 125, 111) 11.51 (m/z 180, 154, 176) 11.59 (m/z 155, 145, 154) 11.60 (m/z 145, 160, 176) 11.69 (m/z 176, 169, 168) 11.75 (m/z 111, 125, 168) 11.88 (m/z 159, 145, 176) 12.00 1-Tetradecene 12.17 Tetradecane 12.30 (m/z 196, 156, 141) 12.69 Dimethylanthalene (m/z 156, 141, 174) 12.75 (m/z 156, 155, 154) 12.81 (m/z 196, 168, 83) 12.90 (m/z 190, 169, 168) 13.00 (m/z 156, 183, 182) 13.07 (m/z 190, 194, 159) 13.14 (m/z 190, 105, 155) 13.18 (m/z 156, 157, 172) 13.28 1-Pentadecene 13.46 Pentadecane 13.51 (m/z 167, 141, 182) 13.58 2,4-Di-tert-butylphenol 13.71 (m/z 111, 208, 153) 13.82 (m/z 155, 170, 153) 13.89 1-Isopropenylanthalene 13.92 (m/z 153, 97, 204) 14.01 (m/z 168, 169, 155) 14.04 (m/z 170, 155, 153) 14.14 C15 alkene (m/z 183, 210, 182) 14.16 (m/z 157, 204, 208) 14.23 (m/z 197, 196, 155) 14.35 (m/z 204, 208, 170) 14.42 (m/z 204, 105, 224) 14.51 Cetene 14.67 Hexadecane 14.80 (m/z 224, 111, 195) 15.10 (m/z 155, 168, 154) 15.18 (m/z 182, 183, 169) 15.25 (m/z 167, 196, 182) 15.32 (m/z 197, 196, 155) 15.36 (m/z 167, 224, 165) 15.39 (m/z 218, 211, 210) 15.48 (m/z 196, 197, 105) 15.57 (m/z 167, 218, 165) 14.80 (m/z 224, 111, 195) 15.66 1-Heptadecene 15.83 Heptadecane 15.95 C17 alkene (m/z 238, 111, 169) 16.06 C17 alkene (m/z 97, 198, 238) 16.25 (m/z 168, 180, 182) 16.30 (m/z 179, 196, 194) 16.38 (m/z 165, 182, 167) 16.43 (m/z 211, 181, 210) 16.48 (m/z 179, 194, 178) 16.53 (m/z 225, 224, 111) 16.54 (m/z 179, 232, 194) 16.62 (m/z 165, 181, 210) 15.95 C17 alkene (m/z 238, 111, 169) 16.76 1-Octadecene 16.91 Octadecane 17.19 (m/z 178, 250, 97) 17.49 (m/z 225, 179, 178) 17.57 (m/z 239, 179, 194) 17.63 (m/z 246, 179, 194) 17.72 (m/z 266, 193, 181) 17.81 1-Nonadecene 17.94 Nonadecane 18.51 (m/z 179, 239, 208) 18.60 (m/z 253, 252, 193) 18.69 (m/z 260, 192, 191) 18.80 1-Eicosene 18.93 Eicosane 19.47 (m/z 253, 274, 252) 19.76 1-Heneicosene 19.87 Heneicosane 20.77 Docosane 21.64 Tricosane 22.47 Tetracosane 23.27 Pentacosane 24.04 Hexacosane 24.84 Heptacosane 25.74 Octacosane 26.79 Nonacosane

(535) The kinematic viscosity of the oil was assessed using ASTM D445 and ASTM D7042 using an Anton Paar SVM3000 Stabinger Viscometer G2. The oil sample had a kinematic viscosity of 28.2 mm²/s, cSt.

(536) The flash point of the oil was measured using ASTM D93A using a Pensky Martens Herzog, Electronic MP329 instrument. The oil had a flashpoint of 11.3° C.

(537) The oil was subjected to distillation according to EN ISO 405. The results are summarized in Table 12.

(538) TABLE-US-00012 TABLE 12 Distillation results of oil sample. Analysis Analysis No. 1 No. 2 Units Receiver temperature 16 16 ° C. Starting Sample Temperature 22.0 22.0 ° C. Initial Boiling Point 37 37 ° C. 25% Recovery 137.7 135.8 ° C. 35% Recovery 163.1 161.8 ° C. 45% Recovery 189.6 188.5 ° C. 55% Recovery 216.1 217.6 ° C. 65% Recovery 244.9 244.4 ° C. 75% Recovery 271.6 270.8 ° C. 80% Recovery 288.9 286 ° C. 85% Recovery — 305 ° C.

(539) The oil sample was further subjected to ¹H-NMR spectroscopy. The ¹H spectra were obtained in CDCl₃ solvent (Goss Scientific D, 99.8%) at ambient laboratory temperature and auto referenced against the solvent peak using the JEOL ECS 400 NMR spectrometer.

(540) The ¹H-NMR spectra are shown in FIG. 20 and FIG. 21. The annotations in FIG. 21 is a guide highlighting certain peaks of interest. The ¹H-NMR spectra generated for the oil sample confirm the presence of saturated, unsaturated and aromatic hydrocarbons. ¹H-NMR indicates the presence of vinyl, internal and vinylidene olefinic functionalities.

(541) The normalized NMR integration values indicate there is 94.8% aliphatic protons (region 0.2-4 ppm), 3.8% olefinic protons (region 4.5-6.0 ppm) and 1.4% aromatic protons (region 6.7-8.3 ppm). This refers to the percentage of proton atoms in the aliphatic saturated, olefinic and aromatic rings only relative to the total proton content. There were no signals observable outside the range

shown in the ¹H-NMR spectra.

(542) The oil sample was further subjected to ¹³C-NMR spectroscopy. The ¹³C-NMR spectra were obtained in CDCl₃ solvent (Goss Scientific D, 99.8%) at ambient laboratory temperature and auto referenced against the solvent peak.

(543) The ¹³C-NMR spectra are shown in FIG. 22 and FIG. 23. The annotations in FIG. 23 is a guide highlighting certain peaks of interest. The ¹³C-NMR spectra generated for the oil sample are dominated by resonances that are consistent with saturated, unsaturated and aromatic hydrocarbons. ¹³C-NMR indicates the presence of vinyl, internal and vinylidene olefinic functionalities. There were no signals observable outside the range shown in the ¹³C-NMR spectra.

Example Implementations

(544) Example 1: A reactor for pyrolysis of plastic feedstock comprising post-consumer and/or post-industrial plastics, the reactor comprising: a reactor vessel defining an internal volume configured for receiving and pyrolyzing the plastic feedstock; and one or more heaters configured for heating the feedstock in the reactor vessel's internal volume to a temperature of 200° C. or more; wherein the one or more heaters are configured for applying energy at a combined energy density between 0.05 and 0.7 kW per pound of pyrolyzed product produced within the reactor.

(545) Example 2: The reactor of any one of the examples herein, particularly Example 1, wherein the one or more heaters are configured for applying energy at a combined energy density between 0.05 and 0.5 kW per pound of pyrolyzed product produced within the reactor.

(546) Example 3: The reactor of any one of the examples herein, particularly Example 1, wherein the internal volume of the reactor vessel is between 100 and 20,000 gallons.

(547) Example 4: The reactor of any one of the examples herein, particularly Example 1, wherein the reactor vessel is configured for maintaining a pressure in its internal volume during pyrolysis that is between -7.5 and 14.5 psig.

(548) Example 5: The reactor of any one of the examples herein, particularly Example 1, wherein the one or more heaters are configured for applying heat to the plastic feedstock in the reactor vessel at a heat density between 5 and 55 W/in.².

(549) Example 6: The reactor of any one of the examples herein, particularly Example 1, wherein the one or more heaters comprise one or more electric heaters.

(550) Example 7: The reactor of any one of the examples herein, particularly Example 6, wherein the one or more electric heaters comprise one or more electric heaters positioned around sides of the reactor vessel.

(551) Example 8: The reactor of any one of the examples herein, particularly Example 6, wherein the one or more electric heaters further comprise one or more electric heaters extending into the interior volume of the reactor vessel.

(552) Example 9: The reactor of any one of the examples herein, particularly Example 1, wherein the one or more heaters comprise an array of electric heaters that are vertically oriented and extend into an interior volume of the reactor vessel.

(553) Example 10: The reactor of any one of the examples herein, particularly Example 1, wherein the reactor vessel includes an agitator configured for stirring the plastic feedstock during pyrolysis.

(554) Example 11: The reactor of any one of the examples herein, particularly Example 10, wherein the agitator is configured to continuously stir the feedstock within the reactor vessel during pyrolysis.

(555) Example 12: The reactor of any one of the examples herein, particularly Example 10, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.2 and 10 m/s.

(556) Example 13: The reactor of any one of the examples herein, particularly Example 10, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.5 and 6 m/s.

(557) Example 14: The reactor of any one of the examples herein, particularly Example 10, wherein the agitator comprises a vertically oriented drive shaft and one or more impellers mounted on the drive shaft.

(558) Example 15: The reactor of any one of the examples herein, particularly Example 14, wherein the one or more impellers each comprise a plurality of impeller blades extending radially outwardly from the drive shaft.

(559) Example 16: The reactor of any one of the examples herein, particularly Example 1, further comprising one or more vapor outlets configured for directing hydrocarbon vapor generated during pyrolysis out of the reactor vessel.

(560) Example 17: The reactor of any one of the examples herein, particularly Example 1, wherein the plastic feedstock is a continuous stream of molten or semi-molten feedstock; and wherein the reactor vessel is configured to pyrolyze the continuous stream of molten or semi-molten feedstock.

(561) Example 18: The reactor of any one of the examples herein, particularly Example 1, wherein the reactor vessel's internal volume is configured for receiving and pyrolyzing the plastic feedstock at an industrial scale.

(562) Example 19: A method for pyrolysis of plastic feedstock comprising post-consumer and/or post-industrial plastics, the method comprising: directing the plastic feedstock into an internal volume of a reactor vessel; and pyrolyzing the plastic feedstock in the internal volume of the reactor vessel; wherein the step of pyrolyzing the plastic feedstock comprises: using one or more heaters to heat the plastic feedstock in the reactor vessel's internal volume to a temperature of 200° C. or more; and using the one or more heaters to apply energy at a combined energy density between 0.05 and 0.7 kW per pound of pyrolyzed product produced within the reactor.

(563) Example 20: The method of any one of the examples herein, particularly Example 19, wherein the step of using the one or more heaters to applying energy comprises using the one or more heaters to apply energy at a combined energy density between 0.05 and 0.5 kW per pound of pyrolyzed product produced within the reactor per hour.

(564) Example 21: The method of any one of the examples herein, particularly Example 19, wherein the internal volume of the reactor vessel is between 100 and 20,000 gallons.

(565) Example 22: The method of any one of the examples herein, particularly Example 19, wherein the reactor vessel is configured for maintaining a pressure in its internal volume during pyrolysis that is between -7.5 and 14.5 psig.

(566) Example 23: The method of any one of the examples herein, particularly Example 19, wherein the one or more heaters are configured for applying heat to the plastic feedstock in the reactor vessel at a heat density between 5 and 55 W/in.^{sup}.2.

(567) Example 24: The method of any one of the examples herein, particularly Example 19, wherein the one or more heaters comprise one or more electric heaters.

(568) Example 25: The method of any one of the examples herein, particularly Example 24, wherein the one or more electric heaters comprise one or more electric heaters positioned around sides of the reactor vessel.

(569) Example 26: The method of any one of the examples herein, particularly Example 24, wherein the one or more electric heaters further comprise one or more electric heaters extending into the interior volume of the reactor vessel.

(570) Example 27: The method of any one of the examples herein, particularly Example 19, wherein the one or more heaters comprise an array of electric heaters that are vertically oriented and extend into an interior volume of the reactor vessel.

(571) Example 28: The method of any one of the examples herein, particularly Example 19, wherein the reactor vessel includes an agitator configured for stirring the plastic feedstock during pyrolysis.

(572) Example 29: The method of any one of the examples herein, particularly Example 28, wherein the agitator is configured to continuously stir the feedstock within the reactor vessel during

pyrolysis.

(573) Example 30: The method of any one of the examples herein, particularly Example 28, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.2 and 10 m/s.

(574) Example 31: The method of any one of the examples herein, particularly Example 28, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.5 and 6 m/s.

(575) Example 32: The method of any one of the examples herein, particularly Example 28, wherein the agitator comprises a vertically oriented drive shaft and one or more impellers mounted on the drive shaft.

(576) Example 33: The method of any one of the examples herein, particularly Example 32, wherein the one or more impellers each comprise a plurality of impeller blades extending radially outwardly from the drive shaft.

(577) Example 34: The method of any one of the examples herein, particularly Example 19, further comprising directing hydrocarbon vapor generated during pyrolysis out of the reactor vessel via one or more vapor outlets provided on the reactor vessel.

(578) Example 35: The method of any one of the examples herein, particularly Example 34, further comprising the steps of: directing the hydrocarbon vapor generated during pyrolysis from the one or more vapor outlets to one or more condensers; and using the one or more condensers to separate the hydrocarbon vapor into a wax product, an oil product, a gas product, or a combination thereof.

(579) Example 36: The method of any one of the examples herein, particularly Example 35, wherein the wax product comprises long-chain hydrocarbons that are solid or semi-solid wax at ambient temperature and pressure.

(580) Example 37: The method of any one of the examples herein, particularly Example 35, wherein the oil product comprises short-chain hydrocarbons that are a liquid at ambient temperature and pressure.

(581) Example 38: The method of any one of the examples herein, particularly Example 35, wherein the gas product comprises hydrocarbons that are non-condensable at ambient temperature and pressure.

(582) Example 39: The method of any one of the examples herein, particularly Example 19, wherein the step of directing the plastic feedstock into an internal volume of a reactor vessel comprises directing a continuous stream of molten or semi-molten feedstock into the internal volume of the reactor vessel; and wherein the step of pyrolyzing the plastic feedstock comprises pyrolyzing the continuous stream of molten or semi-molten feedstock in the reactor vessel.

(583) Example 40: The method of any one of the examples herein, particularly Example 19, wherein the step of directing the plastic feedstock into an internal volume of a reactor vessel comprises: directing the plastic feedstock into one or more extruders, melting the plastic feedstock to produce at least semi-molten feedstock; and directing the at least semi-molten feedstock into the internal volume of the reactor vessel.

(584) Example 41: The method of any one of the examples herein, particularly Example 40, wherein the step of melting the plastic feedstock includes allowing air, steam, and/or low melting-point contaminants to exit the one or more extruders through one or more vents during the melting step.

(585) Example 42: The method of any one of the examples herein, particularly Example 19, wherein the step of pyrolyzing the plastic feedstock in the internal volume of the reactor vessel comprises pyrolyzing the plastic feedstock in the internal volume of the reactor vessel at an industrial scale.

(586) Other advantages which are obvious and which are inherent to the invention will be evident to one skilled in the art. It will be understood that certain features and sub-combinations are of utility and may be employed without reference to other features and sub-combinations. This is

contemplated by and is within the scope of the claims. Since many possible embodiments may be made of the invention without departing from the scope thereof, it is to be understood that all matter herein set forth or shown in the accompanying drawings is to be interpreted as illustrative and not in a limiting sense.

(587) The methods of the appended claims are not limited in scope by the specific methods described herein, which are intended as illustrations of a few aspects of the claims and any methods that are functionally equivalent are intended to fall within the scope of the claims.

(588) Various modifications of the methods in addition to those shown and described herein are intended to fall within the scope of the appended claims. Further, while only certain representative method steps disclosed herein are specifically described, other combinations of the method steps also are intended to fall within the scope of the appended claims, even if not specifically recited. Thus, a combination of steps, elements, components, or constituents may be explicitly mentioned herein or less, however, other combinations of steps, elements, components, and constituents are included, even though not explicitly stated.

Claims

1. A method for pyrolysis of plastic feedstock comprising post-consumer and/or post-industrial plastics, the method comprising: directing the plastic feedstock into an internal volume of a reactor vessel; and pyrolyzing the plastic feedstock in the internal volume of the reactor vessel; wherein the step of pyrolyzing the plastic feedstock comprises: using one or more heaters to heat the plastic feedstock in the reactor vessel's internal volume to a temperature of 200° C. or more; and using the one or more heaters to apply energy at a combined energy density between 0.05 and 0.7 kW per pound of pyrolyzed product produced within the reactor; and wherein the one or more heaters are configured for applying heat to the plastic feedstock in the reactor vessel at a heat density between 5 and 55 W/in.^{sup.2}.
2. The method of claim 1, wherein the step of using the one or more heaters to applying energy comprises using the one or more heaters to apply energy at a combined energy density between 0.05 and 0.5 kW per pound of pyrolyzed product produced within the reactor.
3. The method of claim 1, wherein the internal volume of the reactor vessel is between 100 and 20,000 gallons.
4. The method of claim 1, wherein the reactor vessel is configured for maintaining a pressure in its internal volume during pyrolysis that is between -7.5 and 14.5 psig.
5. The method of claim 1, wherein the one or more heaters comprise one or more electric heaters.
6. The method of claim 5, wherein the one or more electric heaters comprise one or more electric heaters positioned around sides of the reactor vessel.
7. The method of claim 5, wherein the one or more electric heaters further comprise one or more electric heaters extending into the interior volume of the reactor vessel.
8. The method of claim 1, wherein the one or more heaters comprise an array of electric heaters that are vertically oriented and extend into an interior volume of the reactor vessel.
9. The method of claim 1, wherein the reactor vessel includes an agitator configured for stirring the plastic feedstock during pyrolysis.
10. The method of claim 9, wherein the agitator is configured to continuously stir the feedstock within the reactor vessel during pyrolysis.
11. The method of claim 9, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.2 and 10 m/s.
12. The method of claim 9, wherein the agitator is configured to continuously produce average liquid flow velocities inside the reactor vessel between 0.5 and 6 m/s.
13. The method of claim 9, wherein the agitator comprises a vertically oriented drive shaft and one or more impellers mounted on the drive shaft.

14. The method of claim 13, wherein the one or more impellers each comprise a plurality of impeller blades extending radially outwardly from the drive shaft.
15. The method of claim 1, further comprising directing hydrocarbon vapor generated during pyrolysis out of the reactor vessel via one or more vapor outlets provided on the reactor vessel.
16. The method of claim 15, further comprising the steps of: directing the hydrocarbon vapor generated during pyrolysis from the one or more vapor outlets to one or more condensers; and using the one or more condensers to separate the hydrocarbon vapor into a wax product, an oil product, a gas product, or a combination thereof.
17. The method of claim 16, wherein the wax product comprises long-chain hydrocarbons that are solid or semi-solid wax at ambient temperature and pressure.
18. The method of claim 16, wherein the oil product comprises short-chain hydrocarbons that are a liquid at ambient temperature and pressure.
19. The method of claim 16, wherein the gas product comprises hydrocarbons that are non-condensable at ambient temperature and pressure.
20. The method of claim 1, wherein the step of directing the plastic feedstock into an internal volume of a reactor vessel comprises directing a continuous stream of molten or semi-molten feedstock into the internal volume of the reactor vessel; and wherein the step of pyrolyzing the plastic feedstock comprises pyrolyzing the continuous stream of molten or semi-molten feedstock in the reactor vessel.
21. The method of claim 1, wherein the step of directing the plastic feedstock into an internal volume of a reactor vessel comprises: directing the plastic feedstock into one or more extruders, melting the plastic feedstock to produce at least semi-molten feedstock; and directing the at least semi-molten feedstock into the internal volume of the reactor vessel.
22. The method of claim 21, wherein the step of melting the plastic feedstock includes allowing air, steam, and/or low melting-point contaminants to exit the one or more extruders through one or more vents during the melting step.
23. The method of claim 1, wherein the step of pyrolyzing the plastic feedstock in the internal volume of the reactor vessel comprises pyrolyzing the plastic feedstock in the internal volume of the reactor vessel at an industrial scale.
-