

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412778
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Su; Yi-Nien et al.

Method for reducing line end spacing and semiconductor devices manufactured thereof

Abstract

Embodiments of the present disclosure provide methods for forming conductive lines with dielectric cut features. Particularly, embodiments of present disclosure provide a method for forming conductive line pattern using two patterning processes. A line pattern is formed in the first patterning process. A cut pattern is formed over the line pattern in the second patterning process. The cut pattern is formed by forming cut openings with a width smaller than the line width of the line pattern and then filling the cut opening with a mask material.

Inventors: Su; Yi-Nien (Hsinchu, TW), Chen; Yu-Yu (Hsinchu, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Family ID: 78787654

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 17/237008

Filed: April 21, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220102198 A1	Mar. 31, 2022

Related U.S. Application Data

us-provisional-application US 63084303 20200928

Publication Classification

Int. Cl.: H01L21/768 (20060101); H01L21/033 (20060101); H01L21/311 (20060101)

U.S. Cl.:

CPC H01L21/76802 (20130101); H01L21/0338 (20130101); H01L21/31144 (20130101); H01L21/76829 (20130101); H01L21/76877 (20130101);

Field of Classification Search

CPC: H01L (21/76802); H01L (21/0338); H01L (21/31144); H01L (21/76829); H01L (21/76877); H01L (21/28264); H01L (21/76811); H01L (21/76816); H01L (21/0332)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
7879727	12/2010	Postnikov	257/E21.546	G03F 7/40
9209247	12/2014	Colinge et al.	N/A	N/A
9236267	12/2015	De et al.	N/A	N/A
9412817	12/2015	Yang et al.	N/A	N/A
9412828	12/2015	Ching et al.	N/A	N/A
9472618	12/2015	Oxland	N/A	N/A
9502265	12/2015	Jiang et al.	N/A	N/A
9520482	12/2015	Chang et al.	N/A	N/A
9536738	12/2016	Huang et al.	N/A	N/A
9564396	12/2016	Kao	N/A	H01L 21/76897
9576814	12/2016	Wu et al.	N/A	N/A
9608116	12/2016	Ching et al.	N/A	N/A
10727113	12/2019	Hsiao	N/A	H01L 21/823821
2007/0197014	12/2006	Jeon	438/597	H01L 21/0337
2013/0309838	12/2012	Wei et al.	N/A	N/A
2017/0234942	12/2016	Lavangkul	324/253	G01R 33/04
2018/0040546	12/2017	Yu et al.	N/A	N/A
2018/0047674	12/2017	Tsai et al.	N/A	N/A
2019/0103305	12/2018	Liu et al.	N/A	N/A
2020/0258754	12/2019	Lin et al.	N/A	N/A
2020/0279806	12/2019	Lin	N/A	H01L 21/76805

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
103531526	12/2013	CN	H01L 21/76802
110970305	12/2019	CN	N/A

Primary Examiner: Mehta; Ratisha

Background/Summary

BACKGROUND

(1) The semiconductor industry has experienced continuous rapid growth due to constant improvements in the integration density of various electronic components. For the most part, this improvement in integration density has come from repeated reductions in minimum feature size, allowing more components to be integrated into a given chip area. As minimum feature size reduces, the manufacture of these devices has approached and even surpassed the theoretical limits of photolithography equipment. As semiconductor devices continue to shrink, the spacing desired between elements (i.e., the pitch) of a device is less than the pitch that can be manufactured using traditional optical masks and photolithography equipment.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 is a flow chart of a method for manufacturing of a semiconductor device according to embodiments of the present disclosure.

(3) FIGS. 2 to 6, FIGS. 7A-C to FIGS. 12A-C, FIGS. 13-14, and FIGS. 15A-C schematically illustrate a semiconductor device according to the present disclosure at various stages of manufacturing.

(4) FIG. 16A is a schematic plan view of an inter-metal dielectric layer according to embodiments of the present disclosure.

(5) FIG. 16B is a partial enlarged view of the inter-metal dielectric layer of FIG. 16A.

DETAILED DESCRIPTION

(6) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “over,” “top,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be

interpreted accordingly.

(8) Embodiments of the present disclosure provide methods for forming conductive lines with dielectric cut features. Particularly, embodiments of present disclosure provide a method for forming conductive line pattern by first forming a line pattern, then forming a cut pattern over the line pattern. The cut pattern may be formed by forming cut openings with a width smaller than the line width in the line pattern and then filling the cut opening with a mask material.

(9) FIG. 1 is a flow chart of a method **100** for manufacturing of a semiconductor device according to embodiments of the present disclosure. Particularly, the method **100** relates to processes for forming conductive lines in a semiconductor device. FIGS. 2 to 6, FIGS. 7A-C to FIGS. 12A-C, FIGS. 13-14, and FIGS. 15A-C schematically illustrate a semiconductor device **200** at various stages of manufacturing according to the method **100**. FIGS. 2-6, FIG. 7A-12A, FIGS. 13-14, FIG. 15A are schematic perspective view of the semiconductor device **200** at various intermediate stages of forming conductive lines. FIGS. 7B-12B and 15C are cross sectional view of the semiconductor device **200** along the line B-B shown in FIG. 6. FIGS. 7C-12C, and 15C are cross sectional view of the semiconductor device **200** along the line C-C shown in FIG. 6A.

(10) The method **100** relates to patterning and forming conductive lines in a layer dielectric material. In some embodiments, the conductive lines may be part of a metallization structure or an interconnect structure of a semiconductor device. The conductive lines may be formed by an electrically conductive material, such as a metal. For example, the conductive lines formed using the techniques described herein may be used to form conductive interconnects as part of a Back End of Line (BEOL) process or a Front End of Line (FEOL) process.

(11) In some embodiments, the semiconductor device **200** is processed as part of a larger wafer. A singulation process may be applied to scribe line regions of the wafer in order to separate individual semiconductor dies from the wafer.

(12) As shown in FIG. 2, the semiconductor device **200** includes a substrate **202**. In some embodiments, the substrate **202** includes various features formed thereon. For example, the substrate **202** may include active devices, interconnect structures, and the like.

(13) The substrate **202** may include a semiconductor material such as silicon, doped or undoped, or an active layer of a semiconductor-on-insulator (SOI) substrate. The substrate **202** may include other semiconductor materials, such as germanium; a compound semiconductor including silicon carbide, gallium arsenic, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including SiGe, GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP; or combinations thereof. Other substrates, such as multi-layered or gradient substrates, may also be used. Devices (not illustrated), such as transistors, for example planar transistors, field effect transistors (FETs), Fin-FETs, Horizontal Gate All Around (HGAA) FETs, Vertical Gate All Around (VGAA) FETs, diodes, capacitors, resistors, or other suitable devices, may be formed in and/or on an active surface of semiconductor material in the substrate **202**. Interconnect structures, such as interlayer dielectric layers, etch stop layers, IMD layers, may also be included in the substrate **202**.

(14) The semiconductor device **200** may include a dielectric layer **206** formed over the substrate **202**. Conductive lines are formed in the dielectric layer **206** according to the method **100** described herein.

(15) In some embodiments, the dielectric layer **206** is an IMD layer. In some embodiments, the dielectric layer **206** may be formed over an inter-layer dielectric (ILD) layer on the substrate **202**. In other embodiments, the dielectric layer **206** may be an ILD layer formed over source/drain regions or the gate of a transistor (e.g., a FinFET), a dielectric layer in an interconnect structure, or a dielectric layer used in other types of metallization structures. For example, the dielectric layer **206** may be an ILD layer formed over the fins, metal gates, or source/drain regions of one or more FinFETs formed in the substrate **202**.

(16) In some embodiments, the dielectric layer **206** includes one or more layers of dielectric

material, for example, a nitride material such as silicon nitride (SiN), an oxide material such as silicon oxide (SiO), TEOS, BPTEOS, or the like. The dielectric layer **206** may also be a low-k dielectric material, a polymer material, other dielectric material, the like, or combinations thereof. The dielectric layer **206** may be formed by plasma enhanced chemical vapor deposition (PECVD), low pressure CVD (LPCVD), plasma vapor deposition (PVD), or the like.

(17) In some embodiments, the dielectric layer **206** may be in physical contact with the substrate **202**. In other embodiments, any number of intervening layers may be disposed between the dielectric layer **206** and the substrate **202**. Such intervening layers may include IMD layers or dielectric layers, and may have contact plugs, conductive lines, and/or vias formed therein, or may include one or more intermediary layers, e.g., etch stop layers, adhesion layers, etc., combinations thereof, and the like.

(18) In the example of FIG. 2, an optional etch stop layer **204** may be disposed directly under the dielectric layer **206**. The etch stop layer **204** may, for example, act as a stop for an etching process subsequently performed on the dielectric layer **206**. The material and processes used to form the etch stop layer **204** may depend on the material of the dielectric layer **206**. In some embodiments, the etch stop layer **204** may be formed of SiN, SiON, SiCON, SiC, SiOC, SiCN, SiO, other dielectrics, the like, or combinations thereof. The etch stop layer **204** may be formed by plasma enhanced chemical vapor deposition (PECVD), low pressure CVD (LPCVD), plasma vapor deposition (PVD), or the like. Other materials and processes may be used to form the etch stop layer **204**.

(19) The method **100** may be used to patterning the dielectric layer **206** to form conductive lines with cut openings. In the example shown in FIGS. 2-15C, the conductive line pattern is formed in the dielectric layer **206** using two patterning processes. A first patterning process is performed to form mask strips. A second patterning process is followed to form cut features between the mask strips. The mask strips and the cut features are then transferred to the dielectric layer **206** to form line openings with end spacing corresponding to the cut features.

(20) In operation **102** of the method **100**, a first hard mask layer **208** is deposited on the dielectric layer **206**, as shown in FIG. 2. In subsequent processing steps, a pattern is formed on the first hard mask layer **208** using patterning techniques described herein. The patterned first hard mask layer **208** is then used as an etching mask for patterning the dielectric layer **206**. In some embodiments, a material composition of the first hard mask layer **208** may be selected to provide a high etch selectivity with respect to mask layers subsequently formed over the first hard mask layer **208**. The first hard mask layer **208** may include more than one layer and include more than one material.

(21) The first hard mask layer **208** may be formed of a material that includes an oxide material, such as titanium oxide, silicon oxide, or the like; a nitride material, such as silicon nitride, boron nitride, titanium nitride, tantalum nitride; a carbide material, such as tungsten carbide, silicon carbide; a semiconductor material such as silicon; a metal, such as titanium, tantalum; or a combination. In some embodiments, when the dielectric layer **206** includes a low-k material, the first hard mask layer **208** may be formed from an oxide material, or silicon nitride.

(22) The first hard mask layer **208** may be formed using a process such as CVD, ALD, or the like. In some embodiments, the first hard mask layer **208** has a thickness between about 100 angstroms and about 200 angstroms. In other embodiments, the first hard mask layer **208** may have another thickness suitable for critical dimension of the features to be patterned in the dielectric layer **206** and the first hard mask layer **208**.

(23) In operation **104** of the method **100**, a second hard mask layer **210** is formed over the first hard mask layer **208**, as shown in FIG. 2. In subsequent processing steps, a pattern is formed on the second hard mask layer **210** using patterning techniques described herein. The second hard mask layer **210** may be formed of a material that includes an oxide material, such as titanium oxide, silicon oxide, or the like; a nitride material, such as silicon nitride, boron nitride, titanium nitride, tantalum nitride; a carbide material, such as tungsten carbide, silicon carbide; a semiconductor

material such as silicon; a metal, such as titanium, tantalum; or a combination.

(24) As discussed below, the second hard mask layer **210** is used as an etching mask for etching the first hard mask layer **208** and transferring the pattern of the second hard mask layer **210** to the first hard mask layer **208**. The second hard mask layer **210** may be formed from a material different from the first hard mask layer **208**. Alternatively, the first hard mask layer **208** may include more than one layer and include more than one material and may include a material different from the second hard mask layer **210**. In some embodiments, when the first hard mask layer **208** includes an oxide material, or silicon nitride, the second hard mask layer **210** may be formed from titanium nitride, tungsten, silicon, titanium oxide, or a metal oxide.

(25) The second hard mask layer **210** may be formed by a process such as CVD, ALD, or the like. Other processes and materials may be used to form the second hard mask layer **210**. In some embodiments, the second hard mask layer **210** has a thickness between about 100 angstroms and about 300 angstroms. In other embodiments, the second hard mask layer **210** may have another thickness suitable for critical dimension of the features to be patterned in the dielectric layer **206**, in the first hard mask layer **208**, or in the second hard mask layer **210**.

(26) In operation **106** of the method **100**, a third hard mask layer **212** is formed over the second hard mask layer **210**, as shown in FIG. 2. In subsequent processing steps, a pattern is formed on the third hard mask layer **212** using patterning techniques described herein. The patterned third hard mask layer **212** is then used as an etching mask for patterning the second hard mask layer **210**.

(27) The third hard mask layer **212** may be formed from a material including an oxide material, such as titanium oxide, silicon oxide, or the like; a nitride material, such as silicon nitride, boron nitride, titanium nitride, tantalum nitride; a carbide material, such as tungsten carbide, silicon carbide; a semiconductor material such as silicon; a metal, such as titanium, tantalum; or a combination. The third hard mask layer **212** may include more than one layer and include more than one material, and may include a material different from the second hard mask layer **210**. In some embodiments, when the second hard mask layer **210** includes titanium nitride, tungsten, silicon, titanium oxide, or a metal oxide, the third hard mask layer **212** may be formed from an oxide material, or silicon nitride.

(28) The third hard mask layer **212** may be formed using a process such as CVD, ALD, or the like. In some embodiments, a material composition of the third hard mask layer **212** may be determined to provide a high etch selectivity with respect to other layers such as the first hard mask layer **208**, the second hard mask layer **210**, a protective mask layer **214** described below, or other layers.

(29) In some embodiments, the third hard mask layer **212** has a thickness between about 100 angstroms and about 300 angstroms. In other embodiments, the third hard mask layer **212** may have another thickness suitable for critical dimension of the features to be patterned in the dielectric layer **206**, in the first hard mask layer **208**, in the second hard mask layer **210**, or in the third hard mask layer **212**.

(30) In operation **108** of the method **100**, the protective mask layer **214** is formed over the third hard mask layer **212**, as shown in FIG. 2. In subsequent processing steps, a pattern is formed on the protective mask layer **214** using patterning techniques described herein. The patterned protective mask layer **214** is then used as an etching mask for patterning the third hard mask layer **212**.

(31) The protective mask layer **214** may be formed from a suitable dielectric material. In some embodiments, the protective mask layer **214** is a layer of a carbon material, such as a carbon-containing polymer material, e.g., a spin-on-carbon (SOC) material or the like, a layer of carbon deposited using a CVD process, or another type of carbon material. The protective mask layer **214** may include more than one layer and include more than one material.

(32) The protective mask layer **214** may be formed by a suitable process, such as CVD, ALD, Plasma-Enhanced Atomic Layer Deposition (PEALD), spin-on coating, or the like. In some embodiments, the protective mask layer **214** has a thickness between about 200 angstroms and about 500 angstroms. In other embodiments, the protective mask layer **214** may have another

thickness suitable for critical dimension of the features to be patterned in the dielectric layer **206**, in the first hard mask layer **208**, in the second hard mask layer **210**, in the third hard mask layer **212**, or in the protective mask layer **214**.

(33) In operation **110** of the method **100**, a photoresist structure **216** is formed over the protective mask layer **214**, as shown in FIG. 2. In one embodiment, the photoresist structure **216** may be selected to be suitable for an extreme ultraviolet (EUV) photolithography. The photoresist structure **216** shown in FIG. 2 includes an anti-reflection coating (ARC) layer **218** formed over the protective mask layer **214**, a backside anti-reflective coating (BARC) layer **220** formed over the ARC layer **218**, and a photoresist layer **222** formed over the BARC layer **220**. The photoresist structure **216** may be referred to as tri-layer photoresist structure. In other embodiments, one or both of the ARC layer **218** and BARC layer **220** may be omitted forming a double-layer photoresist structure, or a mono-layer photoresist structure.

(34) The ARC layer **218** may be a material such as silicon oxycarbide (SiOC), silicon, silicon oxynitride, titanium oxide, silicon oxide, silicon nitride, a polymer, or a combination thereof. The ARC layer **218** contains a material that is patternable and/or has a composition tuned to provide anti-reflection properties. The ARC layer **218** may be formed by a spin coating process. In other embodiments, the ARC layer **218** may be formed by another suitable deposition process. The ARC layer **218** may have a thickness between about 50 angstroms and about 300 angstroms.

(35) The BARC layer **220** may have a composition that provides anti-reflective properties and/or hard mask properties for the lithography process. In one embodiment, the BARC layer **220** includes a silicon containing layer, e.g., silicon hard mask material. The BARC layer **220** may include a silicon-containing inorganic polymer. In other embodiment, the BARC layer **220** includes a siloxane polymer, e.g., a polymer having a backbone of O—Si—O—Si. The silicon ratio of the BARC layer **220** may be selected to control the etch rate. In other embodiments, the BARC layer **220** may include silicon oxide, e.g., spin-on glass (SOG), silicon nitride, silicon oxynitride, polycrystalline silicon, a metal-containing organic polymer material that contains metal such as titanium, titanium nitride, aluminum, and/or tantalum; and/or other suitable materials. The BARC layer **220** may be omitted when there is a good adhesion between the ARC layer **218** and the photoresist layer **222**. The BARC layer **220** may have a thickness between about 50 angstroms and about 300 angstroms.

(36) The photoresist layer **222** may be a positive photoresist layer or a negative photoresist layer. In some embodiments, the photoresist layer **222** is made of Poly methyl methacrylate (PMMA), poly methyl glutarimide (PMGI), Phenol formaldehyde resin (DNQ/Novolac) or SU-8. In one embodiment, the photoresist layer **222** may have a thickness between about 200 angstroms and about 500 angstroms.

(37) In operation **114** of the method **100**, the photoresist layer **222** is patterned using a photolithography process, as shown FIG. 3. In some embodiments, the photoresist layer **222** may be patterned using an extreme ultraviolet (EUV) lithography process, which uses extreme ultraviolet radiation or soft x-ray, i.e. radiation with wavelength shorter than 130 nm.

(38) As shown in FIG. 3, the photoresist layer **222** is patterned to form a plurality of photoresist strips **222s** separated by a plurality of openings **222o**. The plurality of openings **222o** expose the BARC layer **220** if present or the ARC layer **218** if the BARC layer **220** is not present.

(39) The openings **222o** may be parallel to each other. Adjacent openings **222o** may be separated by the photoresist strips **222s**. In some embodiments, the openings **222o** and the photoresist strips **222s** may extend lengthwise along the Y-axis. Each of the openings **222o** may have a width **W1** that is perpendicular to the lengthwise direction, i.e. along the X-axis. Each of the plurality of photoresist strips **222s** may have a width **W2** along the X-axis.

(40) In some embodiments, the openings **222o** correspond to openings for conductive lines to be formed in the dielectric layer **206**. The width **W1** of the openings **222o** corresponds to the minimal line width, i.e. line width CD, of the semiconductor device to be formed. In some embodiments, the

width **W1** is between about 15 nm and about 25 nm. The width **W2** of the photoresist strips **222s** corresponds to the minimal line to line spacing, i.e. line to line spacing **CD**, of the semiconductor device to be formed. In some embodiments, the width **W2** is between about 15 nm and about 25 nm.

(41) Even though a single photolithographic patterning process is described in the operation **112**, two or more photolithographic patterning processes, i.e., multi-patterning, may be used to allow for a smaller pitch of patterned features. Other photolithographic techniques, including additional or different steps, are within the scope of this disclosure.

(42) In operation **114** of the method **100**, the pattern of the photoresist layer **222** is transferred to the third hard mask layer **212**, as shown in FIG. 4. In some embodiments, the pattern of the photoresist layer **222** is transferred to the third hard mask layer **212** using one or more anisotropic etching processes to etch through the BARC layer **220**, the ARC layer **218**, the protective mask layer **214**, and the third hard mask layer **212**, sequentially.

(43) In some embodiments, the BARC layer **220** is patterned using the patterned photoresist layer **222** as a mask. As a result, the pattern of the photoresist layer **222** is transferred to the BARC layer **220** forming a patterned BARC layer **220**. After the BARC layer **220** is patterned, the ARC layer **218** is patterned using the patterned BARC layer **220**. The BARC layer **220** and the ARC layer **218** may be patterned using plasma processes, for example by plasma with one or more process gases such as CF.sub.4, CH.sub.2F.sub.2, CH.sub.3F, CHF.sub.3, Cl.sub.2, Ar, O.sub.2, N.sub.2, NH.sub.3, H.sub.2, another type of process gas, or a combination thereof. The etching process may be anisotropic, so that the openings **222o** in the photoresist layer **222** are extended through the ARC layer **218** and have about the same sizes in the ARC layer **218** as they do in the photoresist layer **222**.

(44) The pattern of the ARC layer **218** is then transferred to the protective mask layer **214** in an etching process. The etching process may be anisotropic, so that the openings in the ARC layer **218** are extended through the protective mask layer **214** and have about the same sizes in the protective mask layer **214** as in the ARC layer **218**. The etching process that etches the protective mask layer **214** may include a wet etching process, a dry etching process, or a combination thereof. The plasma etching process may include one or more process gases such as CF.sub.4, CH.sub.2F.sub.2, CH.sub.3F, CHF.sub.3, Cl.sub.2, Ar, **02**, another type of process gas, or a combination thereof. For example, in some embodiments, fluorine-comprising process gases such as CF.sub.4, CH.sub.2F.sub.2, CH.sub.3F, or CHF.sub.3 may be used to etch layers formed from some dielectric materials, and chlorine-comprising process gases such as Cl.sub.2 may be used to etch layers formed from materials such as Si or TiN. Other etching techniques may be used in other embodiments. During the etching of the protective mask layer **214**, the patterned ARC layer **218** may be consumed, and third hard mask layer **212** may be at least partially consumed.

(45) The pattern of the protective mask layer **214** is transferred to the third hard mask layer **212** in an etching process. The etching process may be anisotropic, so that the openings in the protective mask layer **214** are extended through the third hard mask layer **212** and have about the same sizes in the third hard mask layer **212** as they do in the protective mask layer **214**. As shown in FIG. 4, after operation **114**, a plurality of mask strips **212s** are formed in the third hard mask layer **212**. Neighboring mask strips **212s** are separated by openings **212o** formed through the third hard mask layer **212**. The openings **212o** have about the same size of the opening **222o**. The mask strips **212s** have about the same size of the photoresist strips **222s**.

(46) The etching process that etches the third hard mask layer **212** may include a wet etching process, a dry etching process, or a combination thereof. The plasma etching process may include one or more process gases such as CF.sub.4, CH.sub.3F, C.sub.4F.sub.6, C.sub.4F.sub.8, other suitable gas, or a combination thereof. Other etching techniques may be used in other embodiments.

(47) After the etching of the third hard mask layer **212**, portions of the protective mask layer **214**

may remain. In some embodiments, the remaining portions of the protective mask layer **214** may be removed using, for example, a wet etching process. In other embodiments, the remaining portions of the protective mask layer **214** are left remaining over the patterned third hard mask layer **212**, for example, to be used as a protective layer.

(48) In operation **116** of the method **100**, a second protective mask layer **224** is deposited over the patterned third mask layer **212**, as shown in FIG. **5**. The openings **212o**, formed in operation **114**, in the third mask layer **212** is filled with material of the second protective mask layer **224**.

(49) The second protective mask layer **224** may be similar to the protective mask layer **214**. The second protective mask layer **224** is a layer of a carbon material, such as a carbon-containing polymer material, e.g., SOC material or the like, a layer of carbon deposited using a CVD process, or another type of carbon material. The second protective mask layer **224** may be formed by a suitable process, such as CVD, ALD, PEALD, spin-on coating, or the like. In some embodiments, the second protective mask layer **224** has a thickness between about 200 angstroms and about 500 angstroms. In some embodiments, the thickness of the second protective mask layer **224** is measured from a top surface of the third mask layer **212**. In other embodiments, the second protective mask layer **224** may have another thickness suitable for critical dimension of the features to be patterned in the dielectric layer **206**, in the first hard mask layer **208**, in the second hard mask layer **210**, in the third hard mask layer **212**, or in the second protective mask layer **224**.

(50) In operation **118** of the method **100**, a second photoresist structure **226** is formed over the second protective mask layer **224**, as shown in FIG. **6**. The photoresist structure **226** may be similar to the photoresist structure **216**. In one embodiment, the photoresist structure **226** is a tri-layer photoresist including an ARC layer **228**, a BARC layer **230**, and a photoresist layer **232**.

(51) The ARC layer **228** may be a material such as SiOC, silicon, silicon oxynitride, titanium oxide, silicon oxide, silicon nitride, a polymer, or a combination. The ARC layer **228** may have a thickness between about 50 angstroms and about 300 angstroms.

(52) The BARC layer **230** may have a composition that provides anti-reflective properties and/or hard mask properties for the lithography process. In one embodiment, the BARC layer **230** includes a silicon containing layer, e.g., silicon hard mask material. The BARC layer **230** may have a thickness between about 50 angstroms and about 300 angstroms.

(53) The photoresist layer **232** may be a positive photoresist layer or a negative photoresist layer. In some embodiments, the photoresist layer **232** is made of PMMA, PMGI, Phenol formaldehyde resin (DNQ/Novolac) or SU-8. In one embodiment, the photoresist layer **232** may have a thickness between about 200 angstroms and about 500 angstroms.

(54) In operation **120** of the method **100**, the photoresist layer **232** is patterned using a photolithography process to form one or more cut openings, as shown FIGS. **7A-C**. In some embodiments, the photoresist layer **232** may be patterned using an EUV lithography process.

(55) As shown in FIG. **7A**, the photoresist layer **232** is patterned to form one or more cut openings **232ol**, **232os**. The cut openings **232ol**, **232os** expose the BARC layer **230** if present or the ARC layer **228** if the BARC layer **230** is not present.

(56) In some embodiments, the cut openings **232ol**, **232os** may extend lengthwise along the X-axis. The cut openings **232ol**, **232os** may have varied length **L1**, **L2** respectively along the X-axis. The cut openings **232ol**, **232os** may have substantially the same width **W3**, that is perpendicular to the lengthwise direction, e.g., along the Y-axis.

(57) The cut openings **232ol**, **232os** in the photoresist layer **232** are intended to facilitate cut features between the mask strips **212s** in the third hard mask layer **212**. Accordingly, the cut openings **232ol**, **232os** are formed in locations corresponding to line end spacings between the adjacent conductive lines to be formed in the dielectric layer **206**. Each cut opening **232ol**, **232os**, may extend lengthwise along the X-axis across one or more openings **212o**, which are formed in the third hard mask layer **212** and filled with materials of the second protective mask layer **224**. In some embodiments, each cut opening **232ol**, **232os**, also would intersect with the mask strips **212s**

on both sides of the openings **212o**. As shown in FIG. 7B, the cut opening **232ol** extends along the X-axis covering two openings **212o** and intersecting with three of the mask strips **212s**. The cut opening **232os**, crossing one opening **212o**, would facilitate formation of a cut feature for a single conductive line. The cut opening **232ol**, crossing two openings **212o**, would facilitate formation of cut features in two neighboring conductive lines. Cut openings of longer length and crossing more openings **212o** may be formed according to the circuit layout.

(58) In some embodiments, the width **W3** of the cut openings **232ol**, **232os** is formed wider than the intended width of the cut features to be formed in the dielectric layer **206**. In some embodiments, the width **W3** may be similar to the line width **CD** of the conductive lines to be formed, or the line width **W1** of the openings **212o**. As discussed below, during subsequent pattern transferring, the width of the cut openings will reduce from the width of the cut openings in the photoresist layer **232** to a desirable narrower width in the third hard mask layer **212** and the second protective mask layer **224**, therefore, reducing line-end spacing between the conductive lines to be formed. As shown in FIG. 7C, the width of cut openings to be formed in the third hard mask layer **212** and the second protective mask layer **224** have a width **W4**, which is narrower the width **W3** of the cut openings **232ol**, **232os**. In some embodiments, the width **W4** is in a range less than about 50% of the width **W1** of the openings **212o**.

(59) In some embodiments, lengths of the cut openings in the photoresist layer **232** may also be longer than intended length of cut openings to be formed in the third hard mask layer **212** and the second protective mask layer **224**. As shown in FIG. 7B, the length **L2** of the cut opening **232ol** is longer than intended length **L3** of cut openings to be formed in the third hard mask layer **212** and the second protective mask layer **224**. The added length in the cut openings **232ol**, **232os** would provide tolerance for size reduction in the subsequent pattern transfer operations.

(60) In operation **122** of the method **100**, the pattern of the photoresist layer **232** is transferred to the third hard mask layer **212**, as shown in FIGS. 8A-C. In some embodiments, the pattern of the photoresist layer **232** is transferred to the third hard mask layer **212** using one or more etching processes to etch through the BARC layer **230**, the ARC layer **228**, the second protective mask layer **224**, and the third hard mask layer **212**, sequentially.

(61) In some embodiments, width of cut openings is reduced from the width **W3** of the cut openings **232ol**, **232os** to the width **W4** during one or more steps of pattern transfer from the photoresist layer **232** to the second protective mask layer **224**. In some embodiments, lengths of the cut openings are reduced accordingly during one or more steps of pattern transfer from the photoresist layer **232** to the second protective mask layer **224**.

(62) In the embodiment shown in FIGS. 8A-C, width of the cut openings is reduced from the width **W3** of the cut openings **232ol**, **232os** to the width **W4** of cut openings **228ol** during pattern transfer from the photoresist layer **232** to the ARC layer **228**. Alternatively, the pattern transfer from the photoresist layer **232** to the ARC layer **228** may be an anisotropic etch for a direct pattern transfer, while the width of the cut openings is reduced during the pattern transfer from the ARC layer **228** to the second protective mask layer **224**. In another embodiment, both of the pattern transfer from the photoresist layer **232** to the ARC layer **228** and the pattern transfer from the ARC layer **228** to the second protective mask layer **224** reduce the width of the cut openings.

(63) In some embodiments, the BARC layer **230**, if present, is patterned using the patterned photoresist layer **232** as a mask. As a result, the pattern of the photoresist layer **232** is transferred to the BARC layer **230** forming a patterned BARC layer **230**. The BARC layer **230** may be patterned using plasma processes, for example by plasma with one or more process gases such as CF.sub.4, CH.sub.2F.sub.2, CH.sub.3F, CHF.sub.3, Cl.sub.2, Ar, O.sub.2, N.sub.2, NH.sub.3, H.sub.2, another type of process gas, or a combination thereof.

(64) The ARC layer **228** is patterned using the patterned photoresist layer **232** or patterned BARC layer **230** if present. In some embodiments, the ARC layer **228** may be patterned using plasma processes, for example by plasma with one or more process gases such as CF.sub.4,

CH.sub.2F.sub.2, CH.sub.3F, CHF.sub.3, Cl.sub.2, Ar, O.sub.2, N.sub.2, NH.sub.3, H.sub.2, another type of process gas, or a combination thereof.

(65) In some embodiments, the etching gas may include two or more etchants with different etching properties to control the dimension of the openings formed in the ARC layer **228** relative to the dimension of the openings in the etching mask, such as the patterned photoresist layer **232** and/or the patterned BARC layer **230**. In some embodiments, the etching gas includes a direct etching agent and a dimension reduction etching agent. The direct etching agent, when used alone transfers a pattern directly from the mask to the layer being etched. The dimension reduction etching agent, when used alone, forms openings with reduced dimensions compared to the features in the mask. The ratio of the direct etching agent and the dimension reduction etching agent can be adjusted to achieve a target dimension reduction. In some embodiments, the direct etching agent includes CF.sub.4 and the dimension reduction etching agent includes CHF.sub.3. The ratio of the CF.sub.4 and CHF.sub.3 in the etching gas is selected to achieve a desired ratio of opening width reduction.

(66) As shown in FIGS. **8A-8C**, cut openings **228ol**, **228os** are formed through the ARC layer **228**. The width **W4** of the cut openings **228ol**, **228os** is smaller than the width **W3** of the cut openings **232ol**, **232os**. In some embodiments, the ratio of the width **W4** and the width **W3** is in a range between 80% and 40%. In some embodiments, lengths **L3**, **L4** of the cut openings **228os**, **228ol** also reduces by similar dimension. For example, if the width **W4** of cut openings **228os**, **228ol** is 12 nm narrower than the width **W3** of the cut openings **232ol**, **232os**, the length **L3**, **L4** of the cut openings **228os**, **228ol** is about 12 nm shorter than the length **L1**, **L2** of the cut openings **232ol**, **232os** respectively. The etching gas may include CF.sub.4 and CHF.sub.3. The ratio of CF.sub.4 and CHF.sub.3 is selected to achieve a desired width reduction. In some embodiments, the ratio of CF.sub.4 and CHF.sub.3 is in a range between about 1:0.2 to about 0.8:1. A higher ratio of CF.sub.4 and CHF.sub.3 corresponds to a higher ratio of the width **W4** over the width **W3**. For example, when the ratio of CF.sub.4 and CHF.sub.3 is about 1:0, the ratio of the width **W4** over the width **W3** is about 100%. When the ratio of CF.sub.4 and CHF.sub.3 is about 1:1, the ratio of the width **W4** over the width **W3** is about 50%.

(67) The pattern of the ARC layer **228** is then transferred to the second protective mask layer **224** by an etching process. The etching process may be anisotropic, so that the cut openings **228ol**, **228os** in the ARC layer **228** are extended through the second protective mask layer **224** forming cut openings **224ol**, **224os**. The cut openings **224ol**, **224os** expose portions of the mask strips **212s** and the second hard mask layer **210** in areas corresponding to the openings **212o**. The etching process that etches the second protective mask layer **224** may include a wet etching process, a dry etching process, or a combination thereof. In some embodiments, a dry etching process may be a plasma etching process using one or more process gases such as CF.sub.4, CH.sub.2F.sub.2, CH.sub.3F, CHF.sub.3, Cl.sub.2, Ar, O.sub.2, another type of process gas, or a combination.

(68) In some embodiments, the exposed portions of the mask strips **212s** may be removed during the etching process of the ARC layer **228**. In other embodiments, etching process to remove the exposed portion of the mask strips **212s** may be omitted leaving the exposed portions of the mask strips **212s** as part of the mask to be formed in the subsequent operations.

(69) In operation **124**, cut mask **234** is formed within the cut openings **228ol**, **228os** in the ARC layer **228** and the cut openings **224ol**, **224os** in the second protective mask layer **224**, as shown in FIGS. **9A-C** and **11A-C**.

(70) A mask material may be used to fill the cut openings **228ol**, **228os** in the ARC layer **228** and the cut openings **224ol**, **224os** in the second protective mask layer **224** as shown in FIGS. **9A-C**. The mask material may have properties similar to those of the materials of the third hard mask layer **212** so that the cut mask **234** and the mask strips **212s** are used together as an etching mask for patterning the second hard mask layer **210**.

(71) The cut mask **234** may be formed from a material including an oxide material, such as

titanium oxide, silicon oxide, or the like; a nitride material, such as silicon nitride, boron nitride, titanium nitride, tantalum nitride; a carbide material, such as tungsten carbide, silicon carbide; a semiconductor material such as silicon; a metal, such as titanium, tantalum; or a combination. In some embodiments, when the second hard mask layer **210** includes titanium nitride, W, Si, titanium oxide, or a metal oxide, the cut mask **234** may be formed from an oxide material, or silicon nitride.

(72) The cut mask **234** may be formed using a process such as CVD, ALD, or the like. In some embodiments, the cut mask **234** is formed by filling the cut openings **228ol**, **228os** in the ARC layer **228** and the cut openings **224ol**, **224os** in the second protective mask layer **224** by an ALD process.

(73) After filling the cut openings **228ol**, **228os** in the ARC layer **228** and the cut openings **224ol**, **224os** in the second protective mask layer **224**, a planarization process, such as a CMP process is used to expose the ARC layer **228**, as shown in FIGS. **10A-C**.

(74) The ARC layer **228** and the second protective mask layer **224** are subsequently removed to expose the cut mask **234**, as shown in FIGS. **11A-C**. The openings **212o**, which are formed in operation **122** in the third mask layer **212**, are reformed except portions occupied by the cut mask **234**. The cut mask **234** and the mask strips **212s** in the third hard mask layer **212** are then used together to pattern the second hard mask layer **210**.

(75) In operation **126** of the method **100**, the pattern defined by the mask strips **212s** in the third hard mask layer **212** and the cut mask **234** is transferred to the second hard mask layer **210** in an etching process, as shown in FIGS. **12A-C**.

(76) The etching process may be anisotropic, so that the openings **212o** in the third hard mask layer **212** are extended through the second hard mask layer **210** and have about the same sizes in the second hard mask layer **210** as they do in the third hard mask layer **212**. The resulting structure is illustrated in FIGS. **12A-12C**. A pattern including mask strips **210s** and mask cut features **210c** are formed in the second hard mask layer **210**. The mask strips **210s** and the mask cut features **210c** defines a plurality of line openings **210o**. The line openings **210o** are mostly elongated openings segmented by the mask cut features **210c**.

(77) The etching process that etches the second hard mask layer **210** may include a wet etching process, a dry etching process, or a combination thereof. In some embodiments, a dry etching process may be a plasma etching using one or more process gases such as Cl.sub.2, CH.sub.4, N.sub.2, HBr, another type of process gas, or a combination. Other etching techniques may be used in other embodiments. In some embodiments, during the etching of the second hard mask layer **210**, portions of the third hard mask layer **212** and the cut mask **234** may remain.

(78) In operation **128** of the method **100**, the mask strips **212s** in the second hard mask layer **210** and the cut mask **234** are used as an etching mask to extend openings **212o** through the first hard mask layer **208** into the dielectric layer **206**, thus forming openings **208o** in the first hard mask layer **208** and forming openings **206o** in the dielectric layer **206**, as shown in FIGS. **13, 14**. In some embodiments, the openings **206o** may be formed through a portion of the dielectric layer **206** as a part of conductive line patterning process, such as a damascene patterning process.

(79) Etching the dielectric layer **206** may include an anisotropic dry etch process and/or a wet etch process, which etches through the first hard mask layer **208** to the dielectric layer **206**. In some embodiments, the first hard mask layer **208** is etched in a separate etching step than the etching process to form the openings **206o** in the dielectric layer **206**. As shown in FIG. **13**, the pattern in the second hard mask layer **210** is transferred to the first hard mask layer **208**. Unetched portions of the first hard mask layer **208** includes mask strips **208s** and mask cut features **208c**. Unetched portions of the dielectric layer **206** may have a same pattern as the first hard mask layer **208**. Unetched portions of the dielectric layer **206** includes strips **206s** and cut features **206c**. The strips **206s** and the cut features **206c** define the openings **206o**, where conductive lines are to be formed. Because of the direct transferring of the patterns from the first hard mask layer **208** to the dielectric layer **206**, width of the openings **206o** along the X-axis is substantially the same as the width **W1**, and width of the cut features **206c** along the Y-axis is substantially the same as the width **W4**.

(80) After the openings **206o** are patterned, a wet cleaning process may be performed to remove any remaining portions of the first hard mask layer **208**. In some embodiments, additional patterning process may be performed to form via openings **206v** through the dielectric layer **206** and the etch stop layer **204**, as shown in FIG. **14**. The via openings **206v** may expose contacts, metal lines, or other conductive features within beneath the dielectric layer **206**, such as conductive features within the substrate **202** or within another layer beneath the dielectric layer **206**.

(81) In operation **130** of the specification, conductive lines **236l** are formed in the openings **206o** patterned in the dielectric layer **206**, as shown in FIGS. **15A-C**. Conductive vias **236v** may be formed in the via openings **206v**.

(82) As shown in FIGS. **15A** and **15C**, width of the conductive lines **236l** along the X-axis is substantially the same as the width **W1**. Two conductive lines **236l** may extend along the same line that is parallel the Y-axis, separated by one cut feature **206c** at ends of the two conductive lines. As discussed above, the width of the cut features **206c** along the Y-axis is substantially the same as the width **W4**.

(83) In some embodiments, the width **W1** of the conductive lines **236l** corresponds to the line width **CD** in the semiconductor device **200**, and the width **W4** corresponds to the line end **CD** in the semiconductor device **200**. As discussed above, during formation of the cut mask **234**, the width **W4** is reduced to a range between about 80% to about 40% of the width **W1**. Thus, the line end **CD** is smaller than line width **CD** satisfying the design rules for the circuit design. The width **W4** or the line end **CD**, is in a range between about 80% and about 40% of the width **W1** or the line width **CD**. If the line end **CD** is greater than 80% of the line width **CD**, design rules for circuit layout may not be well satisfied. If the line end **CD** is less than 40% of the line width **CD**, the cut features **206c** may not provide enough isolation function between the conductive lines **236l**. In some embodiments, the width **W1**, or the line end **CD** of the semiconductor device **200**, is between about 15 nm to about 25 nm, and the width **W4** is less than about 12 nm, for example, in a range between about 12 nm and about 6 nm.

(84) The conductive lines **236l** and conductive vias **236v** may be formed by filling the openings **206o** and via openings **206v** with a conductive material. The conductive material may include Co, Cu, Ag, Al, TiN, TaN, Ta, Ti, Hf, Zr, Ni, W, Zn, Ca, Au, Mg, Mo, Cr, or the like. The conductive material may be formed by CVD, PVD, plating, ALD, or other suitable technique. In some embodiments, one or more liners, not shown, may be formed along sidewalls and a bottom surface of the openings **206o** and via openings **206v** prior to filling the conductive material, and the conductive lines **236l** and conductive vias **236v** includes one or more liners and the conductive filling material. The liners may include TiO, TiN, TaO, TaN, or the like, and may provide diffusion barrier, adhesion, and/or seed layers for the conductive lines.

(85) Subsequently, a CMP process is performed to remove excessive conductive material and expose the dielectric layer **206**. After operation **130**, interconnect structure or bond pad layer may be formed over the dielectric layer **206** according to the circuit design.

(86) Semiconductor devices according to the present disclosure not only have with improved line end **CD** but also have improved line end profiles. FIG. **16A** is a schematic plan view of an example of the dielectric layer **206** with the conductive lines **236l** according to embodiments of the present disclosure. FIG. **16B** is a partial enlarged view of FIG. **16A**.

(87) As shown in FIG. **16A**, a plurality of conductive lines **236l** are formed in the dielectric layer **206**. The conductive lines **236l** are parallel to each other and neighboring conductive lines **236l** are separated by a dielectric strip **206l**. Each conductive line **236l** is divided into segments **236lu**, **236ld** by a dielectric cut feature **206c**.

(88) As shown in the enlarged view in FIG. **16B**, the segments **236lu**, **236ld** have a line width **W1**. The line end spacing is **W4**, and the line spacing is **W2**. According to embodiments of the present disclosure, the line width **W1** is less than about 25 nm, for example in a range between about 15 nm and about 25 nm. The line end spacing **W4** is in a range between about 80% of **W1** to about

40% of W1. The line spacing W2 is substantially equal to the line width W1, or in a range between about 15 nm and about 25 nm.

(89) Each segment **236d**, **236lu** of the conductive line **236l** has an end portion **236e** of facing the cut feature **206c**. The end portion **236e** has a relatively flat profile compared to the line ends formed by the current technology. Particularly, the end portion **236e** has a profile including two corners **236a** connected by a flat section **236f**. The corners **236a** may have a radius R1. In some embodiments, the radius R1 may be less than about 20% of the line width W1 and the flat section **236f** may be greater than about 60% of the line width W1. With relative flat end portion **236e**, the segments **236d**, **236lu** of the conductive lines **236l** improves performance of the semiconductor devices.

(90) Various embodiments or examples described herein offer multiple advantages over the state-of-art technology. Embodiments of the present disclosure shrinks line end spacing to better satisfy design rules for circuit layout. Conductive lines according to the present disclosure also provide a flatter line end profile for the conductive lines near cut features, therefore, improving device performance.

(91) It will be understood that not all advantages have been necessarily discussed herein, no particular advantage is required for all embodiments or examples, and other embodiments or examples may offer different advantages.

(92) Some embodiments of the present disclosure provide a method. The method includes depositing a first hard mask layer over a dielectric layer, forming a plurality of mask strips in the first hard mask layer, wherein the plurality of mask strips are separated by a plurality of openings, filling a first material in the plurality of openings between the plurality of mask strips, forming a cut opening through the first material, filling the cut opening with a second material, removing the first material to expose the second material and the plurality of mask strips, and patterning the dielectric layer using the plurality of mask strips and the second material.

(93) Some embodiments of the present disclosure provide a method. The method include depositing a first hard mask layer, depositing a second hard mask layer on the first hard mask layer, patterning the second hard mask layer to form a plurality of mask strips over the first hard mask layer, wherein the plurality of mask strips extend along a first direction, depositing a mask layer over the plurality of mask strips and the first hard mask layer, depositing a photoresist over the mask layer, patterning the photoresist to form a cut opening to expose at least one of the plurality of mask strips, forming a cut mask in the cut opening, wherein the cut mask extends along a second direction substantially perpendicular to the first direction, removing the mask layer and the photoresist, and patterning the first hard mask layer using the plurality of mask strips and the cut mask as etching masks.

(94) Some embodiments of the present disclosure provide a semiconductor device. The semiconductor device includes a dielectric layer, and a first conductive line formed in the dielectric layer, and a second conductive line formed in the dielectric layer, wherein the first and second conductive lines extend along the same direction, an end portion of the first conductive line faces an end portion of the second conductive line, an end spacing between the end portions of the first and second conductive lines is less than a line width of the first conductive line, and the line width is less than about 25 nm.

(95) Some embodiments of the present disclosure include a method. The method includes depositing a dielectric layer, patterning the dielectric layer using extreme ultraviolet (EUV) patterning technology to form a first opening and a second opening in the dielectric layer, and filling the first and second openings in the dielectric layer to form a first conductive line and a second conductive line in the dielectric layer, wherein the first and second conductive lines extend along the same direction, an end portion of the first conductive line faces an end portion of the second conductive line, an end spacing between the end portions of the first and second conductive lines is less than a line width of the first conductive line, and the line width is less than about 25

nm.

(96) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method, comprising, depositing a first hard mask layer over a dielectric layer; forming a plurality of mask strips in the first hard mask layer, wherein the plurality of mask strips are separated by a plurality of openings; filling a first material in the plurality of openings between the plurality of mask strips; forming a cut opening through the first material and above the dielectric layer, wherein forming the cut opening in the first material comprises: forming a first opening having a first width in a photoresist layer; and performing an etching process using a dimension reduction etching agent to transfer the first opening in the photoresist layer to the first material to form the cut opening, wherein the cut opening has a second width, and the second width is smaller than the first width; depositing a BARC layer over the first material prior to forming the first opening in the photoresist layer; etching the BARC layer using the dimension reduction etching agent to form a second opening having the second width; and patterning the first material using the BARC layer; filling the cut opening with a second material; removing the first material to expose the second material and the plurality of mask strips; and patterning the dielectric layer using the plurality of mask strips and the second material.
2. The method of claim 1, further comprising: filling a conductive material in the dielectric layer after patterning the dielectric layer.
3. The method of claim 2, wherein the plurality of mask strips extend lengthwise along a first direction, the cut opening extends lengthwise along a second direction perpendicular to the first direction, and the cut opening intersects with two or more mask strips.
4. The method of claim 1, wherein filling the first material in the plurality of openings comprises forming a protective mask layer over the plurality of mask strips using the first material.
5. The method of claim 1, further comprising: prior to forming first hard mask layer, depositing a second hard mask layer on the dielectric layer; and depositing a third hard mask layer on the second hard mask layer, wherein the first hard mask layer is formed on the third hard mask layer.
6. The method of claim 5, wherein patterning the dielectric layer comprises: patterning the third hard mask layer using the plurality of mask strips and the second material; patterning the second hard mask layer using the third hard mask layer; and patterning the dielectric layer using the second hard mask layer.
7. The method for claim 1, wherein a width of the first opening substantially equals a width of the plurality of mask strips, and a width of the cut opening is in a range between about 80% to about 40% of the width of the first opening.
8. The method of claim 1, wherein a width of the first opening substantially equals a width of the plurality of mask strips.
9. A method, comprising: depositing a first hard mask layer; depositing a second hard mask layer on the first hard mask layer; patterning the second hard mask layer to form a plurality of mask strips over the first hard mask layer, wherein the plurality of mask strips extend along a first direction; depositing a mask layer over the plurality of mask strips and the first hard mask layer; depositing a photoresist layer over the mask layer; patterning the photoresist layer to form a cut

opening to expose at least one of the plurality of mask strips; forming a cut mask in the cut opening, wherein the cut mask extends along a second direction substantially perpendicular to the first direction; and patterning the first hard mask layer using the plurality of mask strips and the cut mask as etching masks.

10. The method of claim 9, wherein forming the cut mask comprising filling the cut opening with a mask material.

11. The method of claim 9, wherein patterning the photoresist layer to form the cut opening comprises: forming a first opening in the photoresist layer, wherein a width of the first opening substantially equals a width of the plurality of mask strips; and forming the cut opening in the mask layer using the photoresist layer as an etching mask using a dimension reduction etching agent so that the cut opening is narrower than the first opening.

12. The method of claim 9, further comprising: forming a first opening in the photoresist layer; forming a second opening in a BARC layer formed on the mask layer using the photoresist layer as an etching mask, wherein the second opening is narrower than the first opening; and forming the cut opening in the mask layer using the BARC layer as an etching mask.

13. The method of claim 12, wherein the cut opening is narrower than the second opening.

14. The method for claim 12, wherein a width of the first opening substantially equals a width of the plurality of mask strips, and a width of the cut opening is in a range between about 80% to about 40% of the width of the first opening.

15. A method, comprising: depositing a dielectric layer; patterning the dielectric layer using extreme ultraviolet (EUV) patterning technology to form a first opening and a second opening in the dielectric layer; and filling the first and second openings in the dielectric layer to form a first conductive line and a second conductive line in the dielectric layer, wherein the first and second conductive lines extend along the same direction, an end portion of the first conductive line faces an end portion of the second conductive line, an end spacing between the end portions of the first and second conductive lines is less than a line width of the first conductive line, and the line width is less than about 25 nm, wherein the end portion of the first conductive line includes a profile comprising: a first corner; a second corner; and a flat portion connecting the first and second corner, wherein a length of the flat portion is between about 60% to about 80% of the line width.

16. The method of claim 15, wherein the end spacing is in a range between about 80% and about 40% of the line width.

17. The method of claim 15, wherein the end spacing is less than 50% of the line width.

18. The method of claim 16, wherein patterning the dielectric layer further comprises forming a third opening in the dielectric layer, and filling the third opening to form a third conductive line parallel to the first conductive line, a line spacing between the first and third conductive lines are substantially equal to the line width.

19. The method of claim 15, wherein a radius of the first corner is less than about 20% of the line width.

20. The method of claim 15, wherein patterning the dielectric layer using extreme ultraviolet (EUV) patterning technology to form the first opening and second opening in the dielectric layer comprises: depositing a first hard mask layer over the dielectric layer; forming a plurality of mask strips in the first hard mask layer, wherein the plurality of mask strips are separated by a plurality of openings; filling a first material in the plurality of openings between the plurality of mask strips; forming a cut opening through the first material and above the dielectric layer; filling the cut opening with a second material; removing the first material to expose the second material and the plurality of mask strips; and patterning the dielectric layer using the plurality of mask strips and the second material.
