

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412842
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Karhade; Omkar G. et al.

Microelectronic structures including bridges

Abstract

Disclosed herein are microelectronic structures including bridges, and related assemblies and methods. In some embodiments, a microelectronic structure may include a substrate with first and second metal layers; a cavity in the substrate, where a portion of the first and second metal layers, are exposed with the portion of the first metal layer partially overlapping the portion of the second metal layer; and a bridge component in the cavity, having a first conductive contact at a first face and a second conductive contact at a second face opposing the first face, the second face towards a bottom surface of the cavity, the portion of the first metal layer is between the second face of the bridge component and the portion of the second metal layer, and the second conductive contact is electrically coupled to the portion of the second metal layer in the cavity.

Inventors: Karhade; Omkar G. (Chandler, AZ), Deshpande; Nitin A. (Chandler, AZ), Bhatia; Mohit (Chandler, AZ), Mallik; Debendra (Chandler, AZ)

Applicant: Intel Corporation (Santa Clara, CA)

Family ID: 78825958

Assignee: Intel Corporation (Santa Clara, CA)

Appl. No.: 18/462600

Filed: September 07, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230420376 A1	Dec. 28, 2023

Related U.S. Application Data

continuation parent-doc US 16902910 20200616 US 11804441 child-doc US 18462600

Publication Classification

Int. Cl.: H01L23/538 (20060101); H01L21/48 (20060101); H01L23/00 (20060101); H01L23/498 (20060101); H01L25/065 (20230101); H01L25/18 (20230101)

U.S. Cl.:

CPC H01L23/5385 (20130101); H01L21/481 (20130101); H01L21/4853 (20130101); H01L21/4857 (20130101); H01L23/49833 (20130101); H01L24/16 (20130101); H01L24/17 (20130101); H01L24/73 (20130101); H01L25/0652 (20130101); H01L25/0655 (20130101); H01L25/18 (20130101); H01L2224/16145 (20130101); H01L2224/16227 (20130101); H01L2224/1703 (20130101); H01L2224/17181 (20130101); H01L2224/73253 (20130101)

Field of Classification Search

CPC: H01L (23/5385); H01L (23/49833); H01L (24/16); H01L (24/17); H01L (25/0652); H01L (25/0655)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5858254	12/1998	Balzer et al.	N/A	N/A
9549468	12/2016	Tsai	N/A	H01L 23/49827
11289412	12/2021	Williamson et al.	N/A	N/A
2003/0057551	12/2002	Datta et al.	N/A	N/A
2012/0234589	12/2011	Furuichi et al.	N/A	N/A
2014/0319522	12/2013	Daubenspeck et al.	N/A	N/A
2016/0343666	12/2015	Deshpande et al.	N/A	N/A
2018/0076103	12/2017	Jeon et al.	N/A	N/A
2018/0158802	12/2017	Yeh et al.	N/A	N/A
2019/0157240	12/2018	Tsai et al.	N/A	N/A
2019/0164879	12/2018	Kanbe	N/A	N/A
2020/0035603	12/2019	Rubin et al.	N/A	N/A
2020/0185292	12/2019	Kwon	N/A	H01L 24/32
2021/0183753	12/2020	Sakuma et al.	N/A	N/A
2021/0202394	12/2020	Lin et al.	N/A	N/A
2021/0272905	12/2020	Karhade et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
WO-2019132965	12/2018	WO	H01L 23/49822

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a continuation of (and claims the benefit and priority under 35 U.S.C. 120 of) U.S. patent application Ser. No. 16/902,910, filed Jun. 16, 2020, entitled “MICROELECTRONIC STRUCTURES INCLUDING BRIDGES,” the disclosure of which is considered part of, and is incorporated by reference in, the disclosure of this application.

BACKGROUND

(1) In conventional microelectronic packages, a die may be attached to an organic package substrate by solder. Such a package may be limited in the achievable interconnect density between the package substrate and the die, the achievable speed of signal transfer, and the achievable miniaturization, for example.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Embodiments will be readily understood by the following detailed description in conjunction with the accompanying drawings. To facilitate this description, like reference numerals designate like structural elements. Embodiments are illustrated by way of example, not by way of limitation, in the figures of the accompanying drawings.

(2) FIG. 1 is a side, cross-sectional view of an example microelectronic structure, in accordance with various embodiments.

(3) FIG. 2 is a side, cross-sectional view of an example microelectronic assembly including the microelectronic structure of FIG. 1, in accordance with various embodiments.

(4) FIGS. 3-10 are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic assembly of FIG. 2, in accordance with various embodiments.

(5) FIGS. 11-16 are side, cross-sectional views of example microelectronic structures, in accordance with various embodiments.

(6) FIGS. 17-25 are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure of FIG. 14, in accordance with various embodiments.

(7) FIG. 26 is a side, cross-sectional view of an example microelectronic structure, in accordance with various embodiments.

(8) FIGS. 27-28 are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure of FIG. 26.

(9) FIG. 29 is a side, cross-sectional view of an example microelectronic structure, in accordance with various embodiments.

(10) FIGS. 30-31 are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure of FIG. 29.

(11) FIG. 32 is a side, cross-sectional view of an example microelectronic structure, in accordance with various embodiments.

(12) FIGS. 33-34 are side, cross-sectional views of various stages in an example process for the manufacture a microelectronic assembly including the microelectronic structure of FIG. 32.

(13) FIG. 35 is a side, cross-sectional view of an example microelectronic structure, in accordance with various embodiments.

(14) FIGS. 36-52 are side, cross-sectional, exploded views of example microelectronic assemblies,

in accordance with various embodiments.

(15) FIGS. 53-54 are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure of FIG. 52.

(16) FIGS. 55-57 are side, cross-sectional, exploded views of example microelectronic assemblies, in accordance with various embodiments.

(17) FIG. 58 is a top view of a wafer and dies that may be included in a microelectronic structure or microelectronic assembly in accordance with any of the embodiments disclosed herein.

(18) FIG. 59 is a side, cross-sectional view of an integrated circuit (IC) device that may include be included in a microelectronic structure or microelectronic assembly in accordance with any of the embodiments disclosed herein.

(19) FIG. 60 is a side, cross-sectional view of an IC device assembly that may include a microelectronic structure or microelectronic assembly in accordance with any of the embodiments disclosed herein.

(20) FIG. 61 is a block diagram of an example electrical device that may include a microelectronic structure or microelectronic assembly in accordance with any of the embodiments disclosed herein.

DETAILED DESCRIPTION

(21) Disclosed herein are microelectronic structures including bridges, as well as related assemblies and methods. In some embodiments, a microelectronic structure may include a substrate and a bridge in a cavity of the substrate. Microelectronic components may be coupled to both the substrate and the bridge.

(22) To achieve high interconnect density in a microelectronics package, some conventional approaches require costly manufacturing operations, such as fine-pitch via formation and first-level interconnect plating in substrate layers over an embedded bridge, done at panel scale. The microelectronic structures and assemblies disclosed herein may achieve interconnect densities as high or higher than conventional approaches without the expense of conventional costly manufacturing operations. Further, the microelectronic structures and assemblies disclosed herein offer new flexibility to electronics designers and manufacturers, allowing them to select an architecture that achieves their device goals without excess cost or manufacturing complexity.

(23) In the following detailed description, reference is made to the accompanying drawings that form a part hereof wherein like numerals designate like parts throughout, and in which is shown, by way of illustration, embodiments that may be practiced. It is to be understood that other embodiments may be utilized, and structural or logical changes may be made, without departing from the scope of the present disclosure. Therefore, the following detailed description is not to be taken in a limiting sense.

(24) Various operations may be described as multiple discrete actions or operations in turn, in a manner that is most helpful in understanding the claimed subject matter. However, the order of description should not be construed as to imply that these operations are necessarily order dependent. In particular, these operations may not be performed in the order of presentation. Operations described may be performed in a different order from the described embodiment. Various additional operations may be performed, and/or described operations may be omitted in additional embodiments.

(25) For the purposes of the present disclosure, the phrase “A and/or B” means (A), (B), or (A and B). For the purposes of the present disclosure, the phrase “A, B, and/or C” means (A), (B), (C), (A and B), (A and C), (B and C), or (A, B, and C). The phrase “A or B” means (A), (B), or (A and B). The drawings are not necessarily to scale. Although many of the drawings illustrate rectilinear structures with flat walls and right-angle corners, this is simply for ease of illustration, and actual devices made using these techniques will exhibit rounded corners, surface roughness, and other features.

(26) The description uses the phrases “in an embodiment” or “in embodiments,” which may each refer to one or more of the same or different embodiments. Furthermore, the terms “comprising,”

“including,” “having,” and the like, as used with respect to embodiments of the present disclosure, are synonymous. When used to describe a range of dimensions, the phrase “between X and Y” represents a range that includes X and Y.

(27) FIG. 1 is a side, cross-sectional view of an example microelectronic structure **100**. The microelectronic structure **100** may include a substrate **102** and a bridge component **110** in a cavity **120** at a “top” face of the substrate **102**. The substrate **102** may include a dielectric material **112** and conductive material **108**, with the conductive material **108** arranged in the dielectric material **112** (e.g., in lines and vias, as shown) to provide conductive pathways through the substrate **102**. In some embodiments, the dielectric material **112** may include an organic material, such as an organic buildup film. In some embodiments, the dielectric material **112** may include a ceramic, an epoxy film having filler particles therein, glass, an inorganic material, or combinations of organic and inorganic materials, for example. In some embodiments, the conductive material **108** may include a metal (e.g., copper). In some embodiments, the substrate **102** may include layers of dielectric material **112**/conductive material **108**, with lines of conductive material **108** in one layer electrically coupled to lines of conductive material **108** in an adjacent layer by vias of the conductive material **108**. A substrate **102** including such layers may be formed using a printed circuit board (PCB) fabrication technique, for example. A substrate **102** may include N such layers, where N is an integer greater than or equal to one; in the accompanying drawings, the layers are labeled in descending order from the face of the substrate **102** closest to the cavity **120** (e.g., layer N, layer N-1, layer N-2, etc.). Although a particular number and arrangement of layers of dielectric material **112**/conductive material **108** are shown in various ones of the accompanying figures, these particular numbers and arrangements are simply illustrative, and any desired number and arrangement of dielectric material **112**/conductive material **108** may be used. For example, although FIG. 1 and others of the accompanying drawings do not illustrate conductive material **108** in layer N-1 under the bridge component **110**, conductive material **108** may be present in layer N-1 under the bridge component **110**. Further, although a particular number of layers are shown in the substrate **102** (e.g., five layers), these layers may represent only a portion of the substrate **102**, and further layers may be present (e.g., layers N-5, N-6, etc.).

(28) As noted above, a microelectronic structure **100** may include a cavity **120** at the “top” face of the substrate **102**. In the embodiment of FIG. 1, the cavity **120** extends through a surface insulation material **104** at the “top” face, and the bottom of the cavity is provided by the “topmost” dielectric material **112**. The surface insulation material **104** may include a solder resist and/or other dielectric materials that may provide surface electrical insulation and may be compatible with solder-based or non-solder based interconnects, as appropriate. In other embodiments, a cavity **120** in a substrate **102** may extend into the dielectric material **112**, as discussed further below. The cavity **120** may have a tapered shape, as shown in FIG. 1, narrowing towards the bottom of the cavity **120**. The substrate **102** may include conductive contacts **114** at the “top” face that are coupled to conductive pathways formed by the conductive material **108** through the dielectric material **112**, allowing components electrically coupled to the conductive contacts **114** (not shown in FIG. 1, but discussed below with reference to FIG. 2) to circuitry within the substrate **102** and/or to other components electrically coupled to the substrate **102**. The conductive contacts **114** may include a surface finish **116**, which may protect the underlying material of the conductive contact from corrosion. In some embodiments, the surface finish **116** may include nickel, palladium, gold, or a combination thereof. The conductive contacts **114** may be located at the “top” face and outside the cavity **120**; as shown, the surface insulation material **104** may include openings at the bottom of which the surface finishes **116** of the conductive contacts **114** are exposed. In FIG. 1, solder **106** (e.g., a solder ball) may be disposed in the openings, and in conductive contact with the conductive contacts **114**. As shown in FIG. 1 and others of the accompanying drawings, these openings in the surface insulation material **104** may be tapered, narrowing towards the conductive contacts **114**. In some embodiments, the solder **106** on the conductive contacts **114** may be first-level interconnects, while

in other embodiments, non-solder first-level interconnects may be used to electrically couple the conductive contacts **114** to another component. As used herein, a “conductive contact” may refer to a portion of conductive material (e.g., one or more metals) serving as part of an interface between different components; although some of the conductive contacts discussed herein are illustrated in a particular manner in various ones of the accompanying drawings, any conductive contacts may be recessed in, flush with, or extending away from a surface of a component, and may take any suitable form (e.g., a conductive pad or socket).

(29) A bridge component **110** may be disposed in the cavity **120**, and may be coupled to the substrate **102**. This coupling may include electrical interconnects or may not include electrical interconnects; in the embodiment of FIG. **1**, the bridge component **110** is mechanically coupled to the dielectric material **112** of the substrate **102** by an adhesive **122** (e.g., a die-attach film (DAF)) between the “bottom” face of the bridge component **110** and the substrate **102**, while other types of couplings are described elsewhere herein. The bridge component **110** may include conductive contacts **118** at its “top” face; as discussed below with reference to FIG. **2**, these conductive contacts **118** may be used to electrically couple the bridge component **110** to one or more other microelectronic components. The bridge component **110** may include conductive pathways (e.g., including lines and vias, as discussed below with reference to FIG. **59**) to the conductive contacts **118** (and/or to other circuitry included in the bridge component **110** and/or to other conductive contacts of the bridge component **110**, as discussed below). In some embodiments, the bridge component **110** may include a semiconductor material (e.g., silicon); for example, the bridge component **110** may be a die **1502**, as discussed below with reference to FIG. **58**, and may include an integrated circuit (IC) device **1600**, as discussed below with reference to FIG. **59**. In some embodiments, the bridge component **110** may be an “active” component in that it may contain one or more active devices (e.g., transistors), while in other embodiments, the bridge component **110** may be a “passive” component in that it does not contain one or more active devices. The bridge component **110** may be manufactured so as to permit a greater density of interconnects than the substrate **102**. Consequently, the pitch **202** of the conductive contacts **118** of the bridge component **110** may be less than the pitch **198** of the conductive contacts **114** of the substrate **102**. When multiple microelectronic components are coupled to the bridge component **110** (e.g., as discussed below with reference to FIG. **2**), these microelectronic components may use the electrical pathways through the bridge component **110** (and may use other circuitry within the bridge component **110**, when present) to achieve a higher density interconnection between them, relative to interconnections made via the conductive contacts **114** of the substrate **102**.

(30) The dimensions of the elements of a microelectronic structure **100** may take any suitable values. For example, in some embodiments, the thickness **138** of the metal lines of the conductive contacts **114** may be between 5 microns and 25 microns. In some embodiments, the thickness **128** of the surface finish **116** may be between 5 microns and 10 microns (e.g., 7 microns of nickel and less than 100 nanometers of each of palladium and gold). In some embodiments, the thickness **142** of the adhesive **122** may be between 2 microns and 10 microns. In some embodiments, the pitch **202** of the conductive contacts **118** of the bridge component **110** may be less than 70 microns (e.g., between 25 microns and 70 microns, between 25 microns and 65 microns, between 40 microns and 70 microns, or less than 65 microns). In some embodiments, the pitch **198** of the conductive contacts **114** may be greater than 70 microns (e.g., between 90 microns and 150 microns). In some embodiments, the thickness **126** of the surface insulation material **104** may be between 25 microns and 50 microns. In some embodiments, the height **124** of the solder **106** above the surface insulation material **104** may be between 25 microns and 50 microns. In some embodiments, the thickness **140** of the bridge component **110** may be between 30 microns and 200 microns. In some embodiments, a microelectronic structure **100** may have a footprint that is less than 100 square millimeters (e.g., between 4 square millimeters and 80 square millimeters).

(31) A microelectronic structure **100**, like that of FIG. **1** and others of the accompanying drawings,

may be included in a larger microelectronic assembly. FIG. 2 illustrates an example of such a microelectronic assembly **150**, which may include one or more microelectronic components **130** having conductive contacts **134** coupled to the conductive contacts **118** of the bridge component **110** (e.g., by solder **106** or another interconnect structure) and conductive contacts **132** coupled to the conductive contacts **114** of the substrate **102** (e.g., by solder **106** or another interconnect structure, as discussed above). FIG. 2 illustrates two microelectronic components **130** (the microelectronic components **130-1** and **130-2**), but a microelectronic assembly **150** may include more or fewer microelectronic components **130**. Although FIG. 2 depicts the microelectronic components **130-1/130-2** as substantially “covering” the proximate surface of the microelectronic structure **100**, this is simply an illustration, and need not be the case. Further, although FIGS. 1 and 2 (and others of the accompanying drawings) depict microelectronic structures **100**/microelectronic assemblies **150** that include a single bridge component **110** in a substrate **102**, this is simply for ease of illustration, and a microelectronic structure **100**/microelectronic assembly **150** may include multiple bridge components **110** in a substrate **102**.

(32) The microelectronic components **130** may include conductive pathways (e.g., including lines and vias, as discussed below with reference to FIG. 59) to the conductive contacts **132/134** (and/or to other circuitry included in the microelectronic component **130** and/or to other conductive contacts of the microelectronic component **130**, not shown). In some embodiments, a microelectronic component **130** may include a semiconductor material (e.g., silicon); for example, a microelectronic component **130** may be a die **1502**, as discussed below with reference to FIG. 58, and may include an IC device **1600**, as discussed below with reference to FIG. 59. In some embodiments, the microelectronic component **130** may be an “active” component in that it may contain one or more active devices (e.g., transistors), while in other embodiments, the microelectronic component **130** may be a “passive” component in that it does not contain one or more active devices. In some embodiments, for example, a microelectronic component **130** may be a logic die. More generally, the microelectronic components **130** may include circuitry to perform any desired functionality. For example, one or more of the microelectronic components **130** may be logic dies (e.g., silicon-based dies), and one or more of the microelectronic components **130** may be memory dies (e.g., high bandwidth memory). As discussed above with reference to FIG. 1, when multiple microelectronic components **130** are coupled to the bridge component **110** (e.g., as shown in FIG. 2), these microelectronic components **130** may use the electrical pathways through the bridge component **110** (and may use other circuitry within the bridge component **110**, when present) to achieve a higher density interconnection between them, relative to interconnections made via the conductive contacts **114** of the substrate **102**.

(33) As used herein, a “conductive contact” may refer to a portion of conductive material (e.g., metal) serving as an interface between different components; conductive contacts may be recessed in, flush with, or extending away from a surface of a component, and may take any suitable form (e.g., a conductive pad or socket).

(34) In some embodiments, a mold material **144** may be disposed between the microelectronic structure **100** and the microelectronic components **130**, and may also be between the microelectronic components **130** and above the microelectronic components **130** (not shown). In some embodiments, the mold material **144** may include multiple different types of mold materials, including an underfill material between the microelectronic components **130** and the microelectronic structure **100** and a different material disposed above and at side faces of the microelectronic components **130**. Example materials that may be used for the mold material **144** include epoxy materials, as suitable.

(35) The microelectronic assembly **150** also illustrates a surface insulation material **104** at the “bottom” face of the substrate **102** (opposite to the “top” face), with tapered openings in the surface insulation material **104** at the bottoms of which conductive contacts **206** are disposed. Solder **106** may be disposed in these openings, in conductive contact with the conductive contacts **206**. The

conductive contacts **206** may also include a surface finish (not shown). In some embodiments, the solder **106** on the conductive contacts **206** may be second-level interconnects (e.g., solder balls for a ball grid array arrangement), while in other embodiments, non-solder second-level interconnects (e.g., a pin grid array arrangement or a land grid array arrangement) may be used to electrically couple the conductive contacts **206** to another component. The conductive contacts **206**/solder **106** (or other second-level interconnects) may be used to couple the substrate **102** to another component, such as a circuit board (e.g., a motherboard), an interposer, or another IC package, as known in the art and as discussed below with reference to FIG. **60**. In embodiments in which the microelectronic assembly **150** includes multiple microelectronic components **130**, the microelectronic assembly **150** may be referred to as a multi-chip package (MCP). A microelectronic assembly **150** may include additional components, such as passive components (e.g., surface-mount resistors, capacitors, and inductors disposed at the “top” face or the “bottom” face of the substrate **102**), active components, or other components.

(36) FIGS. **3-10** are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic assembly **150** of FIG. **2**, in accordance with various embodiments. Although the operations of the process of FIGS. **3-10** (and the processes of others of the accompanying drawings, discussed below) may be illustrated with reference to particular embodiments of the microelectronic structures **100**/microelectronic assemblies **150** disclosed herein, the method **1000** may be used to form any suitable microelectronic structures **100**/microelectronic assemblies **150**. Operations are illustrated once each and in a particular order in FIGS. **3-10**, but the operations may be reordered and/or repeated as desired (e.g., with different operations performed in parallel when manufacturing multiple microelectronic structures **100**/microelectronic assemblies **150**).

(37) FIG. **3** illustrates an assembly that includes a preliminary substrate **102** including dielectric material **112** and patterned conductive material **108**. The assembly of FIG. **3** may be manufactured using conventional package substrate manufacturing techniques (e.g., lamination of layers of the dielectric material **112**, etc.), and may include layers up to N-1.

(38) FIG. **4** illustrates an assembly subsequent to fabricating an additional Nth layer for the preliminary substrate **102** of FIG. **4**. The assembly of FIG. **4** includes the underlying metal of the conductive contacts **114**. The assembly of FIG. **4** may be manufactured using conventional package substrate manufacturing techniques.

(39) FIG. **5** illustrates an assembly subsequent to forming a layer of surface insulation material **104** on the assembly of FIG. **4**.

(40) FIG. **6** illustrates an assembly subsequent to patterning openings in the surface insulation material **104** of the assembly of FIG. **5** to expose the underlying metal of the conductive contacts **114**, forming the surface finish **116** of the conductive contacts **114**, and forming the cavity **120**. In some embodiments, the openings in the surface insulation material **104** (including the cavity **120**) may be formed by mechanical patterning, laser patterning, dry etch patterning, or lithographic patterning techniques. When a laser or mechanical patterning technique is used to form the cavity **120**, the bottom of the cavity **120** may include undulations having an amplitude between 1 micron and 10 microns; when a lithographic patterning technique is used to form the cavity **120**, the bottom of the cavity **120** may include undulations having an amplitude that is less than 1 micron. In some embodiments in which the cavity **120** is laser-patterned, some edge roughness due to laser beam overlap may be present (e.g., with an amplitude between 1 micron and 25 microns).

(41) FIG. **7** illustrates an assembly subsequent to performing a clean operation on the assembly of FIG. **6**, and forming the solder **106** (e.g., microballs) on the conductive contacts **114**.

(42) FIG. **8** illustrates an assembly subsequent to attaching the bridge component **110** to the exposed dielectric material **112** of the cavity **120** of the assembly of FIG. **7**, using the adhesive **122**. In some embodiments, the adhesive **122** may be a DAF, and attaching the bridge component **110** may include performing a film cure operation. The assembly of FIG. **8** may take the form of the

microelectronic structure **100** of FIG. **1**.

(43) FIG. **9** illustrates an assembly subsequent to attaching the microelectronic components **130** to the assembly of FIG. **8**. In some embodiments, this attachment may include a thermocompression bonding (TCB) operation. In some embodiments, additional solder may be provided on the conductive contacts **118**, the conductive contacts **132**, and/or the conductive contacts **134** before the TCB operation.

(44) FIG. **10** illustrates an assembly subsequent to providing the mold material **144** to the assembly of FIG. **9**. As noted above, in some embodiments, the mold material **144** of FIG. **10** may include multiple different materials (e.g., a capillary underfill material between the microelectronic components **130** and the microelectronic structure **100**, and a different material over the microelectronic components **130**). The assembly of FIG. **10** may take the form of the microelectronic assembly **150** of FIG. **2**. As discussed above, the mold material **144** may include an underfill material (e.g., a capillary underfill material).

(45) Various ones of FIGS. **3-57** illustrate example microelectronic structures **100**/microelectronic assemblies **105** having various features. The features of these microelectronic structures **100**/microelectronic assemblies **150** may be combined with any other features disclosed herein, as suitable, to form a microelectronic structure **100**/microelectronic assembly **150**. For example, any of the microelectronic structures **100** disclosed herein may be coupled to one or more microelectronic components **130** (e.g., as discussed above with reference to FIGS. **2-10**) to form a microelectronic assembly **150**, and any of the microelectronic assemblies **150** disclosed herein may be manufactured separately from their constituent microelectronic structures **100**. A number of elements of FIGS. **1** and **2** are shared with FIGS. **3-57**; for ease of discussion, a description of these elements is not repeated, and these elements may take the form of any of the embodiments disclosed herein.

(46) A microelectronic structure **100** may include a cavity **120** that extends through a surface insulation material **104** at a “top” face of the substrate **102** (e.g., as discussed above with reference to FIG. **1**). In some embodiments, the dielectric material **112** of the substrate **102** may provide the bottom of the cavity **120** (e.g., as discussed above with reference to FIG. **1**), while in other embodiments, another material may provide a bottom of the cavity **120**. For example, FIGS. **11** and **12** illustrate a microelectronic structure **100** including a metal layer **146** to which the bridge component **110** is coupled by adhesive **122**. The metal layer **146** may extend up the (angled) side faces of the cavity **120**, as shown in FIG. **11**, or may be located only below the bridge component **110**/adhesive **122**, as shown in FIG. **12**. In some embodiments, the metal layer **146** may include aluminum (which may be sputtered onto an assembly like that of FIG. **7**) or a nickel-palladium-gold multilayer (which may be deposited onto an assembly like that of FIG. **7** by an electroless deposition technique). In an embodiment like that of FIG. **12**, the initially deposited metal layer **146** may be patterned after attachment of the bridge component **110** to remove the metal layer **146** not shielded by the bridge component **110**/adhesive **122**. In some embodiments, a thickness of the metal layer **146** may be less than a thickness **138** of the underlying metal of the conductive contacts **114**, as shown. In embodiments like those of FIGS. **11** and **12**, the adhesive **122** may be an epoxy material. In some such embodiments, the epoxy adhesive **122** may be a ultraviolet (UV)-curable epoxy (also referred to as a “snap-curable” epoxy) that, upon exposure to UV radiation after deposition, quickly cross-links in place (without requiring a long thermal cure). The metal layer **146** may act as a reflective surface during this UV exposure, enabling a desired scattering and distribution of the UV radiation to fully cross-link the epoxy. The use of a UV-curable epoxy as the adhesive **122** may allow the bridge component **110** to be secured in place quickly so that the shift of the bridge component **110** that typically occurs during subsequent processing operations may be mitigated or eliminated.

(47) FIG. **13** illustrates another embodiment in which a microelectronic structure **100** includes a metal to which the bridge component **110** is coupled by adhesive **122**; in FIG. **13**, however, the

metal is a metal pad **148**, coplanar with the underlying metal of the conductive contacts **114**, and having a same thickness **138**. In some such embodiments, the metal pad **148** may present a roughened copper surface to which an adhesive **122** (e.g., a DAF) may readily bond.

(48) The microelectronic structures **100** of FIGS. **1** and **11-13** may allow manufacturers to avoid expensive and complex manufacturing operations typically required for high-density interconnect structures (e.g., ultraviolet (UV) or carbon dioxide laser machining, first-level interconnect plating, etc.) and thus may speed development of new structures and reduce cost.

(49) In some embodiments, a microelectronic structure **100** may include a cavity **120** that extends through a surface insulation material **104** at a “top” face of the substrate **102** and into the dielectric material **112** of the substrate **102**. For example, FIGS. **14-16** illustrate microelectronic structures **100** including cavities **120** that extend into the dielectric material **112** and whose bottoms are provided by the conductive material **108** (e.g., a metal in the N-1 layer). Further, FIGS. **14-16** illustrate microelectronic structures **100** including a metal layer **146** to which the bridge component **110** is coupled by adhesive **122**. The metal layer **146** may extend up the (angled) side faces of the cavity **120**, as shown in FIGS. **14** and **15**, or may be located only below the bridge component **110**/adhesive **122**, as shown in FIG. **16**. In some embodiments, the metal layer **146** may include aluminum (which may be sputtered onto an assembly like that of FIG. **7**), gold, or a nickel-palladium-gold multilayer (which may be deposited onto an assembly like that of FIG. **7** by an electroless deposition technique). In an embodiment like that of FIG. **16**, the initially deposited metal layer **146** may be patterned after attachment of the bridge component **110** to remove the metal layer **146** not shielded by the bridge component **110**/adhesive **122**. In some embodiments, a thickness of the metal layer **146** may be less than a thickness **138** of the underlying metal of the conductive contacts **114**, as shown. In embodiments like those of FIGS. **14-16**, as discussed above with reference to FIGS. **11-12**, the adhesive **122** may be an epoxy material (e.g., a UV-curable epoxy).

(50) In the embodiment of FIG. **15**, the adhesive **122** may include a peripheral adhesive **122-1** and a central adhesive **122-2**. The peripheral adhesive **122-1** may be a UV-curable epoxy, as discussed above, while the central adhesive **122-2** may be a thermally cured epoxy. In the manufacture of the microelectronic structure **100** of FIG. **15**, the peripheral adhesive **122-1** may be cured first by exposure to UV radiation (e.g., as discussed below with reference to FIGS. **17-25**, and then the resulting assembly may be subject to a thermal treatment to cure the central adhesive **122-2**. As noted above, the use of a UV-curable epoxy as (or as part of) the adhesive **122** may allow the bridge component **110** to be secured in place quickly so that the shift of the bridge component **110** that typically occurs during subsequent processing operations may be mitigated or eliminated, dramatically improving the yield and ease of later assembly operations (e.g., attaching microelectronic components **130**).

(51) FIGS. **17-25** illustrate various stages in an example process for the manufacture of the microelectronic structure **100** of FIG. **14**, in accordance with various embodiments. FIG. **17** illustrates an assembly subsequent to patterning openings in the surface insulation material **104** of the assembly of FIG. **5** to expose the underlying metal of the conductive contacts **114**. In some embodiments, the openings in the surface insulation material **104** (including the cavity **120**) may be formed by mechanical patterning, laser patterning, dry etch patterning, or lithographic patterning techniques.

(52) FIG. **18** illustrates an assembly subsequent to applying a mask material **158** over the assembly of FIG. **18**. In some embodiments, the mask material **158** may include a dry film resist (DFR) or a polyethylene terephthalate (PET) film, and may be laminated on.

(53) FIG. **19** illustrates an assembly subsequent to forming the cavity **120** in the assembly of FIG. **18**. The cavity **120** may be formed through the mask material **158**, as shown, and any suitable technique may be used to form the cavity **120** (e.g., laser drilling). Cleaning operations (e.g., water cleaning and/or plasma etch cleaning) may follow the formation of the cavity **120**.

(54) FIG. 20 illustrates an assembly subsequent to forming a metal layer **146** on the assembly of FIG. 19. The metal layer **146** may include any of the materials disclosed herein, and may be deposited using any suitable technique (e.g., aluminum deposited by sputtering).

(55) FIG. 21 illustrates an assembly subsequent to removing the mask material **158** from the assembly of FIG. 20, and consequently removing the portion of the metal layer **146** on the mask material **158**. For example, when the mask material **158** is a PET film, the mask material **158** may be peeled off; when the mask material **158** is a DFR, the mask material **158** may be stripped.

(56) FIG. 22 illustrates an assembly subsequent to depositing uncured adhesive **156** on the metal layer **146** at the bottom of the cavity **120** of the assembly of FIG. 21. When multiple types of adhesives **122** are to be used (e.g., as discussed above with reference to FIG. 15, the multiple types of uncured adhesive **156** may be deposited in a desired pattern. Alternately, a single type of uncured adhesive **156** (e.g., an uncured peripheral adhesive **122-1**) may be deposited initially, and another type of uncured adhesive (e.g., an uncured center adhesive **122-2**) may be provided later (e.g., by capillary underfill after attachment of the bridge component **110**).

(57) FIG. 23 illustrates an assembly subsequent to using a bond head **152** to bring the bridge component **110** (along with solder **106** on the conductive contacts **118**) into contact with the uncured adhesive **156** of the assembly of FIG. 22. When the bridge component **110** is properly positioned, UV sources **154** (e.g., a ring of light-emitting diodes (LEDs)) of the bond head **152** may shine UV radiation on the uncured adhesive **156**, cross-linking the uncured adhesive **156** and resulting in the adhesive **122**.

(58) FIG. 24 illustrates an assembly subsequent to retracing the bond head **152** and performing a thermal cure (e.g., at the panel level) of the assembly of FIG. 24.

(59) FIG. 25 illustrates an assembly subsequent to forming the surface finish **116** and the solder **106** (e.g., microballs) on the conductive contacts **114** of FIG. 24. The resulting assembly may take the form of the microelectronic structure **100** of FIG. 14.

(60) Other manufacturing processes may be used to fabricate the microelectronic structures **100** of FIGS. 14-16. For example, instead of applying a mask material **158** before the formation of the metal layer **146**, no mask material **158** may be used; instead, the metal layer **146** may be formed after the cavity **120** is formed, and the excess metal layer **146** may be removed after the bridge component **110** is attached and before the solder **106** is provided (resulting in a microelectronic structure **100** like that of FIG. 16). In another process, the solder **106** may be provided after the cavity **120** is formed, but before the bridge component **110** is attached; after the thermal cure of FIG. 24, the resulting assembly may be “flash etched” to remove the excess metal layer **146**.

Additionally, in some embodiments, a “bump flattening” operation may be performed after formation of the solder **106**; the assembly may be subject to a controlled “downward” force at a controlled temperature to achieve a desired height profile of the solder **106**.

(61) Other techniques may be used to control the stand-off between the microelectronic structure **100** and the microelectronic components **130**, instead of or in addition to the techniques utilizing a UV-curable adhesive **122** discussed above. For example, FIG. 26 is a side, cross-sectional view of an example microelectronic structure **100** that includes metal-cored solder balls **164** in contact with the conductive contacts **114** (e.g., instead of solder only, as illustrated in some of the preceding drawings). A metal-cored solder ball **164** may include a metal ball **162** (e.g., including copper) that has a surface finish (e.g., nickel, a nickel-palladium-gold multilayer, etc.) to mitigate corrosion, and a thin layer of solder **106** coating the metal ball **162**. In some embodiments, the diameter of the metal ball **162** may be between 10 microns and 300 microns (e.g., between 50 microns and 70 microns, or between 60 microns and 70 microns). In some embodiments, the thickness of the layer of solder **106** on the metal ball **162** may be between 1 microns and 15 microns; as shown in FIG. 26, after reflow of the solder **106** of the metal-cored solder ball **164**, the solder **106** may flow down towards the conductive contact **114**. As shown in FIG. 26, the metal ball **162** may occupy the majority of the volume of the corresponding opening in the surface insulation material **104**, and

may extend above a top surface of the surface insulation material **104**.

(62) FIGS. **27-28** are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure **100** of FIG. **26**. FIG. **27** illustrates an assembly subsequent to printing a layer of flux **160** on the conductive contacts **114** of the assembly of FIG. **6**, and placing metal-cored solder balls **164** on the flux **160**. FIG. **28** illustrates an assembly subsequent to performing a solder reflow (and deflux) to melt the solder **106** around the metal ball **162** of the assembly of FIG. **27**, and then attaching the bridge component **110** to the exposed dielectric material **112** of the cavity **120** using the adhesive **122**, resulting in the microelectronic structure **100** of FIG. **26**. Although a single adhesive **122** is shown in FIGS. **26** and **28**, and the cavity **120** is shown as having a particular depth and bottom material in FIGS. **26-28**, any of the embodiments of these features disclosed herein may be used. The small volume of solder **106** included in the metal-cored solder balls **164** may result in little change of the height or profile of the metal-cored solder balls **164** after the solder reflow operation. FIGS. **26-28** also illustrate solder **106** on the conductive contacts **118** of the bridge component **110**; in some embodiments, this solder **106** (e.g., a tin-based solder) may be microbumps provided on the bridge component **110** prior to attachment of the bridge component **110** to the substrate **102**. Attachment of the microelectronic components **130** (e.g., as discussed above with reference to FIGS. **2-10**) may then be performed on the microelectronic structure **100** of FIG. **25**, aided by the predictable height of the metal-cored solder balls **164** and the solid “backstop” they provide.

(63) FIGS. **29** and **32** illustrate further techniques may be used to control the stand-off between the microelectronic structure **100** and the microelectronic components **130**, instead of or in addition to the techniques utilizing a UV-curable adhesive **122** discussed above. FIG. **29** is a side, cross-sectional view of an example microelectronic structure **100** that includes multi-melting point solder balls **170** in contact with the conductive contacts **114**. A multi-melting point solder ball **170** may include a core of high-temperature solder **168** and a thin layer of low-temperature solder **166** coating the high-temperature solder **168**. As used herein, the terms “high-temperature solder” and “low-temperature solder” are used relatively; a high-temperature solder **168** has a higher melting point than a low-temperature solder **166**. In some embodiments, a high-temperature solder **168** may have a melting point that is greater than 200 degrees Celsius (e.g., between 220 degrees Celsius and 300 degrees Celsius), while a low-temperature solder **166** may have a melting point that is less than 200 degrees Celsius (e.g., between 112 degrees Celsius and 190 degrees Celsius). Other combinations may be used (e.g., a high-temperature solder **168** with a melting point of 189 degrees Celsius and a low-temperature solder **166** with a melting point of 117 degrees Celsius, or a high-temperature solder **168** with a melting point of 300 degrees Celsius and a low-temperature solder **166** with a melting point of 230 degrees Celsius). In some embodiments, a high-temperature solder **168** may include tin, silver, or antimony, and a low-temperature solder **166** may include indium, bismuth, zinc, or lead. As shown in FIG. **29**, after reflow of the low-temperature solder **166** of the multi-melting point solder balls **170**, the low-temperature solder **166** may flow down towards the conductive contact **114**. As shown in FIG. **29**, the high-temperature solder **168** may occupy the majority of the volume of the corresponding opening in the surface insulation material **104**, and may extend above a top surface of the surface insulation material **104**. Although FIG. **29** (and FIG. **31**, discussed below) illustrate the high-temperature solder **168** as retaining a spherical shape, this is simply illustrative, and the high-temperature solder **168** may take any of a number of forms. If the high-temperature solder **168** does not undergo reflow during subsequent manufacturing operations, the high-temperature solder **168** may retain a spherical shape or may look like a “flattened” sphere with flatter faces at the bottom (proximate to the conductive contacts **114**) and the top (proximate to the conductive contacts **132** of a microelectronic component **130**, not shown). The “flattened” sphere of high-temperature solder **168** may remain close to the conductive contacts **114** or may float in the solder joint; if the high-temperature solder **168** floats in the solder joint, the orientation of the sphere may change. If the high-temperature solder **168** does undergo reflow

during subsequent manufacturing operations, the high-temperature solder **168** may form a gradient with the low-temperature solder **166** (with more low-temperature solder **166** closer to the conductive contacts **114**) or the high-temperature solder **168** may mix more thoroughly with the low-temperature solder **166**.

(64) FIGS. **30-31** are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure **100** of FIG. **29**. FIG. **30** illustrates an assembly subsequent to printing a layer of flux **160** on the conductive contacts **114** of the assembly of FIG. **6**, and placing multi-melting point solder balls **170** on the flux **160**. FIG. **31** illustrates an assembly subsequent to performing a (low-temperature) solder reflow (and deflux) to melt the low-temperature solder **166** around the core of high-temperature solder **168** of the assembly of FIG. **30**, and then attaching the bridge component **110** to the exposed dielectric material **112** of the cavity **120** using the adhesive **122**, resulting in the microelectronic structure **100** of FIG. **29**. Although a single adhesive **122** is shown in FIGS. **29** and **31**, and the cavity **120** is shown as having a particular depth and bottom material in FIGS. **29-31**, any of the embodiments of these features disclosed herein may be used. The small volume of low-temperature solder **166** included in the multi-melting point solder balls **170** may result in little change of the height or profile of the multi-melting point solder balls **170** after the solder reflow operation. FIGS. **29-31** also illustrate solder **106** on the conductive contacts **118** of the bridge component **110**; in some embodiments, this solder **106** (e.g., a tin-based solder) may be microbumps provided on the bridge component **110** prior to attachment of the bridge component **110** to the substrate **102**. Attachment of the microelectronic components **130** (e.g., as discussed above with reference to FIGS. **2-10**) may then be performed on the microelectronic structure **100** of FIG. **29**, aided by the predictable height of the multi-melting point solder balls **170** and the solid “backstop” they provide.

(65) FIG. **32** is a side, cross-sectional view of an example microelectronic structure **100** that includes metal posts **172** (e.g., copper posts) in contact with the conductive contacts **114**. A surface finish **116** may be disposed at the top face of the metal posts **172**, as shown. As shown in FIG. **32**, the metal posts **172** may largely fill the corresponding openings in the surface insulation material **104**, and may extend above a top surface of the surface insulation material **104**. In some embodiments, the metal posts **172** may extend above the top surface of the surface insulation material **104** by a distance **176** between 20 microns and 30 microns. In some embodiments the metal posts **172** may be undercut relative to the surface finish **116**, as shown in FIG. **32**.

(66) FIGS. **33-34** are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure **100** of FIG. **32**. FIG. **33** illustrates an assembly subsequent to depositing and patterning a layer of surface insulation material **174** (e.g., a photoresist) on the assembly of FIG. **6**. The surface insulation material **174** may be patterned with openings corresponding to the desired locations for the metal posts **172**. FIG. **34** illustrates an assembly subsequent to plating a metal (e.g., copper) on the assembly of FIG. **33** to form the metal posts **172**, forming the surface finish **116**, and then stripping the surface insulation material **174** (and performing a seed etch to remove the metal seed layer used for the plating operation). Subsequently, the bridge component **110** may be attached to the exposed dielectric material **112** of the cavity **120** of the assembly of FIG. **34** using the adhesive **122**, resulting in the microelectronic structure **100** of FIG. **32**. Although a single adhesive **122** is shown in FIG. **32**, and the cavity **120** is shown as having a particular depth and bottom material in FIGS. **32-34**, any of the embodiments of these features disclosed herein may be used. FIGS. **33-34** also illustrate solder **106** on the conductive contacts **118** of the bridge component **110**; in some embodiments, this solder **106** (e.g., a tin-based solder) may be microbumps provided on the bridge component **110** prior to attachment of the bridge component **110** to the substrate **102**. Attachment of the microelectronic components **130** (e.g., as discussed above with reference to FIGS. **2-10**) may then be performed on the microelectronic structure **100** of FIG. **32**, with solder provided on the conductive contacts **132** of the microelectronic components **130** to couple the conductive contacts **132** to the metal posts **172**,

aided by the predictable height of the metal posts **172** and the solid “backstop” they provide.

(67) Although various ones of the drawings herein illustrate the substrate **102** as a coreless substrate (e.g., having vias that all taper in the same direction), any of the substrates **102** disclosed herein may be cored substrates **102**. For example, FIG. **35** illustrates a microelectronic structure **100** having similar features to the microelectronic structure of FIG. **32**, but having a substrate **102** having a core **178** (through which conductive pathways, not shown, may extend). As shown in FIG. **35**, a cored substrate **102** may include vias that taper towards the core **178** (and thus taper in opposite directions at opposite sides of the core **178**).

(68) Other techniques may be used to control the stand-off between the microelectronic structure **100** and the microelectronic components **130**, instead of or in addition to the techniques utilizing a UV-curable adhesive **122** and/or the techniques utilizing various interconnect arrangements on the conductive contacts **114** of the substrate **102**, discussed above. For example, FIGS. **36-41** illustrate exploded views of example microelectronic assemblies **150** including arrangements of high-temperature solder **168** and low-temperature solder **166** to control stand-off, in accordance with various embodiments. In the microelectronic assembly **150** of FIG. **36**, high-temperature solder **168** may be disposed on the conductive contacts **114** of the substrate **102**, and a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **132/134** of the microelectronic components **130**. In some embodiments, the low-temperature solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **132/134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100** (e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may provide taller overall solder height on the conductive contacts **132/134** without side wicking of the solder. The presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height. More generally, the high-temperature solder **168** in the microelectronic assembly **150** of FIG. **36** may serve as a solder stand-off to improve reliability during manufacturing.

(69) In the microelectronic assembly **150** of FIG. **37**, low-temperature solder **166** may be disposed on the conductive contacts **114** of the substrate **102**, and a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **132/134** of the microelectronic components **130**. In some embodiments, the low-temperature solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **132/134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100** (e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may provide taller overall solder height on the conductive contacts **132/134** without side wicking of the solder. As discussed above with reference to FIG. **36**, the presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height. The low-temperature solder **166** on the conductive contacts **134** may provide a higher collapse window on the interconnects to the conductive contacts **134** during manufacturing.

(70) In the microelectronic assembly **150** of FIG. **38**, high-temperature solder **168** may be disposed on the conductive contacts **114** of the substrate **102**, high-temperature solder **168** may be disposed on the conductive contacts **132** of the microelectronic components **130**, and a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **134** of the microelectronic components **130**. In some embodiments, the low-temperature solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100**

(e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may provide taller overall solder height on the conductive contacts **134** without side wicking of the solder. The high-temperature solder **168** may be molten after the bumps of the low-temperature solder **166** have collapsed so as to interfere minimally or not at all with the bonding of the low-temperature solder **166**. The presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height.

(71) As noted above, in some embodiments, the bridge component **110** may include conductive contacts other than the conductive contacts **118** at its “top” face; for example, the bridge component **110** may include conductive contacts **182** at its “bottom” face, as shown in FIGS. 39-57. The conductive contacts **182** of the bridge component **110** may be conductively coupled to conductive contacts **180** at the bottom of the cavity **120** of the substrate **102** (e.g., by solder **106** or another type of interconnect). In some embodiments, the conductive contacts **180** may be at the bottom of corresponding cavities in the dielectric material **112**, as shown. The conductive contacts **180** may include a surface finish **116** at their exposed surfaces, as shown. Direct electrical connections between the substrate **102** and the bridge component **110** (i.e., electrical connections that do not go through a microelectronic component **130**) may enable direct power and/or input/output (I/O) pathways between the substrate **102** and the bridge component **110**, which may result in power delivery benefits and/or signal latency benefits. In some embodiments, the pitch of the conductive contacts **182** may be between 40 microns and 1 millimeter (e.g., between 40 microns and 50 microns, or between 100 microns and 1 millimeter). In embodiments in which the bridge component **110** includes conductive contacts **182** at its “bottom” face to couple to conductive contacts **180** at the bottom of the cavity **120** of the substrate **102**, a dielectric material (e.g., a capillary underfill material) may support these connections; such a material is not shown in various ones of the accompanying drawings for clarity of illustration.

(72) Any of the preceding embodiments may be combined with a bridge component **110** having conductive contacts **118** and conductive contacts **182** at opposing faces. For example, FIG. 39 illustrates an embodiment in which the conductive contacts **182** are coupled to the substrate **102** by solder. In particular, in the microelectronic assembly **150** of FIG. 39, high-temperature solder **168** may be disposed on the conductive contacts **114** of the substrate **102**, a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **132/134** of the microelectronic components **130** (similar to the embodiment of FIG. 36), and a high-temperature solder **168** may be disposed between the conductive contacts **182** of the bridge component **110** and the conductive contacts **180** in the cavity **120** of the substrate **102**. In some embodiments, the low-temperature solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **132/134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100** (e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may allow the bridge component **110** to stay rigidly in place during attachment of the microelectronic components **130**. The presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height.

(73) In the microelectronic assembly **150** of FIG. 40, low-temperature solder **166** may be disposed on the conductive contacts **114** of the substrate **102**, a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **132/134** of the microelectronic components **130** (similar to the embodiment of FIG. 37), and a high-temperature solder **168** may be disposed between the conductive contacts **182** of the bridge component **110** and the conductive contacts **180** in the cavity **120** of the substrate **102**. In some embodiments, the low-temperature

solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **132/134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100** (e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may allow the bridge component **110** to stay rigidly in place during attachment of the microelectronic components **130**. As discussed, the presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height. The low-temperature solder **166** on the conductive contacts **134** may provide a higher collapse window on the interconnects to the conductive contacts **134** during manufacturing.

(74) In the microelectronic assembly **150** of FIG. **41**, high-temperature solder **168** may be disposed on the conductive contacts **114** of the substrate **102**, high-temperature solder **168** may be disposed on the conductive contacts **132** of the microelectronic components **130**, a high-temperature solder **168** may be disposed between a low-temperature solder **166** and the conductive contacts **134** of the microelectronic components **130** (similar to the embodiment of FIG. **38**), and a high-temperature solder **168** may be disposed between the conductive contacts **182** of the bridge component **110** and the conductive contacts **180** in the cavity **120** of the substrate **102**. In some embodiments, the low-temperature solder **166** may be plated on top of the high-temperature solder **168** on the conductive contacts **134**. When the microelectronic components **130** are brought into contact with the microelectronic structure **100** (e.g., during a TCB operation, as discussed herein), only the low-temperature solder **166** may be molten, which may allow the bridge component **110** to stay rigidly in place during attachment of the microelectronic components **130**. The high-temperature solder **168** may be molten after the bumps of the low-temperature solder **166** have collapsed so as to interfere minimally or not at all with the bonding of the low-temperature solder **166**. The presence of the high-temperature solder **168** on the conductive contacts **134** may allow the microelectronic components **130** to make a hard stop on the bridge component **110**, if desired, and the volume of low-temperature solder **166** that will contact the conductive contacts **118** may be selected to achieve a desired solder height.

(75) Although the conductive contacts **180** of FIGS. **39-41** have been illustrated as having a substantially planar surface facing the bridge component **110**, in other embodiments, the conductive contacts **180** may have a non-planar surface. Such embodiments may allow the spacing between the bridge component **110** and the substrate **102** to be adjusted during manufacturing, and thereby make it easier to achieve a desired offset distance between a top face of the bridge component **110** and a top face of the substrate **102** to facilitate attachment of the microelectronic components **130**. For example, FIGS. **42-44** illustrate microelectronic structures in which the conductive contacts **180** have a planar portion **180A** and a non-planar portion **180B**. The planar portions **180A** may be exposed pads of a metal layer in the substrate **102** (e.g., the N-1 layer or another layer) and the non-planar portions **180B** may be placed or otherwise formed on the planar portions **180A**. The non-planar portions **180B** may have a same material composition as the planar portions **180A**, or may have different material compositions. In some embodiments, the non-planar portions **180B** may include copper or gold. In some embodiments, the conductive contacts **180** (planar or non-planar) may span multiple bridge components **110** in contact with a common microelectronic component **130**.

(76) In the embodiment of FIG. **42**, the non-planar portions **180B** have an arcuate shape, and may include multiple wire segments shaped into arcs with the ends of the wires secured (e.g., wirebonded) to the planar portions **180A** (e.g., forming a dome of wires). In the embodiment of FIG. **43**, the non-planar portions **180B** have a pointed shape, with the point facing the bridge component **110**. Such a pointed shape may be formed by ball bonding a bond wire to the planar portion **180A**, and cutting the bond wire to a desired length. In the embodiment of FIG. **44**, the

non-planar portions **180B** have an extended “S” shape, forming a cantilever over the planar portions **180A**. Such a cantilever may be formed by stitch bonding a bond wire to the planar portion **180A**, and then cutting the bond wire to a desired length. Lithographic techniques may be used instead of or in addition to the wirebonding techniques described herein to form the non-planar portions **180B**. In embodiments in which a conductive contact **180** includes a non-planar portion **180B**, solder **106** (as shown in FIGS. **42-44**) or another interconnect structure may conductively couple the non-planar portion **180B** and the conductive contact **182** of the bridge component **110**, and the shapes of the non-planar portions **180B** may allow the z-height of the bridge component **110** in the microelectronic structure to be adjusted during manufacturing to achieve a desired relative positioning of the bridge component **110** and the substrate **102**.

(77) FIGS. **45-47** illustrate additional examples of microelectronic assemblies **150** in which solder having different melting points may be used to improve the ease of manufacturing and the reliability of the interconnections between the elements in a microelectronic assembly **150**. For example, FIG. **45** illustrates an embodiment in which low-temperature solder **166** is disposed on the conductive contacts **116/180** of the substrate **102**, low-temperature solder **166** is disposed on the conductive contacts **132/134** of the microelectronic components **130**, and a high-temperature solder **168** is disposed on the conductive contacts **118** of the bridge component **110**. As discussed above, the hierarchy of solder melting temperatures in such a microelectronic assembly **150** may enable selective melting of the solder. For example, utilizing a low-temperature solder **166** on the “bottom” side of the bridge component **110** may allow TCB attachment of the bridge component **110** to the substrate **102** by applying heat from the “top” side or the “bottom” side. Heating the microelectronic structure **100** from the “bottom” side may heat this low-temperature solder **166** more, and thus may be less likely to melt or soften the high-temperature solder **168** at the “top” side of the bridge component **110**. Such selective melting of the solder may allow a TCB bond head to contact the high-temperature solder **168** on a “top” face of the bridge component **110** to melt the low-temperature solder **166** at the “bottom” face of the bridge component **110** without undesirably attaching the bridge component **110** to the TCB bond head with melted solder.

(78) FIG. **46** illustrates an embodiment similar to that of FIG. **45**, but in which a polymer material **186** (e.g., a joint reinforcement paste) is disposed around the low-temperature solder **166** between the bridge component **110** and the substrate **102**. The use of such a polymer material **186** may help “freeze” the coupling between the bridge component **110** and the substrate **102** in place, easing subsequent manufacturing operations.

(79) FIG. **47** illustrates another embodiment similar to that of FIG. **45**, but in which adhesive dots **190** (e.g., dots of a cured epoxy) are disposed between the “bottom” face of the bridge component **110** and the dielectric material **112** of the substrate **102**. These adhesive dots **190** may be distributed around the low-temperature solder **166**, and may be used instead of or in addition to the polymer material **186** (discussed above with reference to FIG. **46**) to “freeze” the coupling between the bridge component **110** and the substrate **102** in place, easing subsequent manufacturing operations.

(80) In some embodiments, non-solder materials may be used to conductively couple the bridge component **110** and the substrate **102**. For example, FIG. **48** illustrates an embodiment in which a conductive adhesive **184** is used to conductively couple the conductive contacts **182** of the bridge component **110** to the conductive contacts **180** of the substrate **102**. In some embodiments, the conductive adhesive **184** may include a polymer and a conductive filler (e.g., a metal, such as silver, or a conductive polymer), and may be cured to “freeze” the coupling between the bridge component **110** and the substrate **102**.

(81) In some embodiments, the solder materials used to couple the bridge component **110** and the substrate **102** may be selected so as to “freeze” the coupling in place for subsequent manufacturing operations. FIG. **49** illustrates an embodiment in which an intermetallic compound (IMC) or transient liquid phase sintering (TLPS) material **188** is used to conductively couple the conductive contacts **182** of the bridge component **110** to the conductive contacts **180** of the substrate **102**. In

embodiments in which the material **188** is an IMC material, the bridge component **110** may be soldered to the substrate **102** using a solder chemistry in which the initial solder material is quickly converted into a IMC. In some embodiments, such a solder chemistry may include a mix of low-temperature solder particles and high-temperature solder particles suspended in a flux and an epoxy carrier. In embodiments in which the material **188** is a TLPS material, a low-temperature sinterable material (e.g., a copper-tin polymer material having a peak reflow temperature of 220 degrees Celsius) may be heated between the conductive contacts **182** and the conductive contacts **180**, forming a strong metallic bond that will not reflow during subsequent assembly operations. A TLPS material **188** may have a distinct sintered structure with epoxy and IMC trapped in internal pockets.

(82) In some embodiments including conductive contacts **180** in a cavity **120** of a substrate **102**, the conductive contacts **180** may or may not be located at the “deepest” points in the cavity **120**. Such embodiments may advantageously provide greater volume between the bridge component **110** and the substrate **102**, providing a large enough “chip gap” to allow an underfill material to be used between the bridge component **110** and the substrate **102**. For example, FIG. **50** illustrates an embodiment in which the conductive contacts **180** are located in the N-1 layer, and the cavity **120** extends down to the N-2 layer. In some such embodiments, the metal in the N-1 and N-2 layers together may provide a laser stop for a laser drill used to form the cavity **120**, and thus some portions of the cavity **120** may extend down the N-2 layer. FIG. **51** illustrates an embodiment similar to that of FIG. **50**, but in which the conductive contacts **180** are located in the N-2 layer, and some of the bottom surface of the cavity **120** is provided by metal in the N-1 layer. Again, as discussed with reference to FIG. **50**, in some embodiments like that of FIG. **51**, the metal in the N-1 and N-2 layers together may provide a laser stop for a laser drill used to form the cavity **120**, and thus some portions of the cavity **120** may extend down the N-2 layer. The metal of the N-1 layer closest to a conductive contact **180** may provide a ring around that conductive contact **180** so as to avoid an undesirable electrical short if the solder **106** on the conductive contact **180** contacts the nearest N-1 metal.

(83) FIG. **52** illustrates an embodiment in which, like the embodiment of FIG. **51**, the conductive contacts **180** are located in the N-2 layer, but some of the bottom surface of the cavity **120** is provided by the dielectric material **112** underlying the N-1 layer. A substrate **102** like that of FIG. **52** may be fabricated by providing a solid metal portion in the area of the cavity **120** in the N-1 layer (as part of the initial substrate manufacturing process), and performing an initial cavity formation step by laser drilling and stopping on this solid metal portion; the solid metal portion may then be removed (e.g., by etch, and possibly leaving some of the peripheral metal of the solid metal portion behind, as shown in FIG. **52**), and then a second cavity formation step of laser drilling may be performed to expose the conductive contacts **180** in the N-2 layer.

(84) FIG. **53** illustrates another embodiment in which the conductive contacts **180** are located in a metal layer below the N layer (e.g., the N-1 layer, as shown), and some of the bottom surface of the cavity **120** is provided by the dielectric material **112**. In contrast to the embodiment of FIG. **52**, the dielectric material **112** at the bottom of the cavity **120** is the dielectric material **112** underlying the metal layer in which the conductive contacts **180** are disposed (i.e., the top surface of the dielectric material **112** at the bottom of the cavity **120** is coplanar with the bottom surface of the conductive contacts **180**). FIGS. **54-55** are side, cross-sectional views of various stages in an example process for the manufacture of the microelectronic structure of FIG. **53**. FIG. **54** illustrates an assembly subsequent to laser drilling into the assembly of FIG. **7**, stopping at a solid metal portion in the area of the cavity **120** in the N-1 layer (as part of the initial substrate manufacturing process). FIG. **55** illustrates an assembly subsequent to performing a patterned etch of some of the solid metal portion of FIG. **54**, with the remaining metal providing the conductive contacts **180**. A bridge component **110** may then be attached to the assembly of FIG. **55** to form a microelectronic structure **100**, and microelectronic components **130** may be coupled to the microelectronic structure

100 to form the microelectronic assembly **150** of FIG. **53**.

(85) FIG. **56** illustrates another embodiment in which the conductive contacts **180** are located in a metal layer below the N layer (e.g., the N-1 layer, as shown), and some of the bottom surface of the cavity **120** is provided by the dielectric material **112**. In contrast to the embodiment of FIG. **53**, the top surface of the dielectric material **112** at the bottom of the cavity **120** is coplanar with the top surface of the conductive contacts **180**). An embodiment like that of FIG. **56** may also include a metal ring **192**, coplanar with the conductive contacts **180**, proximate to the edges of the cavity **120**, as shown. A substrate **102** like that of FIG. **56** may be fabricated by providing the conductive contacts **180** and the metal ring **192** in the N-1 layer (as part of the initial substrate manufacturing process), and putting a sacrificial film over the area on the N-1 layer corresponding to the cavity **120**; after completion of the initial substrate **102**, a ring corresponding to the edges of the cavity **120** may be laser drilled, stopping on the metal ring **192**, and the sacrificial film (now exposed at its edges) may be released and any material above the sacrificial film may be removed.

(86) Although various ones of the embodiments disclosed herein have been illustrated for embodiments in which the conductive contacts **118** at the “top” face of the bridge component **110** are exposed in the microelectronic structure **100** (i.e., an “open cavity” arrangement), any suitable ones of the embodiments disclosed herein may be utilized in embodiments in which additional layers of the substrate **102** are built up over the bridge component **110**, enclosing the bridge component **110** (i.e., an “embedded” arrangement). For example, FIG. **57** illustrates a microelectronic assembly **150** like that of FIG. **50**, but in which additional dielectric material **112** and metal layers are disposed “above” the bridge component **110**. As shown in FIG. **57**, conductive pads and vias through this “additional” material may be used to allow microelectronic components **130** to conductively couple to the conductive contacts **118** via the intervening material of the substrate **102**. Similarly, any suitable ones of the embodiments disclosed herein may be utilized in such an embedded arrangement.

(87) The microelectronic structures **100** and microelectronic assemblies **150** disclosed herein may be included in any suitable electronic component. FIGS. **58-61** illustrate various examples of apparatuses that may include any of the microelectronic structures **100** and microelectronic assemblies **150** disclosed herein, or may be included in microelectronic structures **100** and microelectronic assemblies **150** disclosed herein, as appropriate.

(88) FIG. **58** is a top view of a wafer **1500** and dies **1502** that may be included in any of the microelectronic structures **100** and microelectronic assemblies **150** disclosed herein. For example, a die **1502** may be included in a microelectronic structure **100**/microelectronic assembly **150** as (or part of) a bridge component **110** and/or a microelectronic component **130**. The wafer **1500** may be composed of semiconductor material and may include one or more dies **1502** having IC structures formed on a surface of the wafer **1500**. Each of the dies **1502** may be a repeating unit of a semiconductor product that includes any suitable IC. After the fabrication of the semiconductor product is complete, the wafer **1500** may undergo a singulation process in which the dies **1502** are separated from one another to provide discrete “chips” of the semiconductor product. The die **1502** may include one or more one or more transistors (e.g., some of the transistors **1640** of FIG. **59**, discussed below), one or more diodes, and/or supporting circuitry to route electrical signals to the transistors, as well as any other IC components. In some embodiments, a die **1502** may be a “passive” die in that it includes no active components (e.g., transistors), while in other embodiments, a die **1502** may be an “active” die in that it includes active components. In some embodiments, the wafer **1500** or the die **1502** may include a memory device (e.g., a random access memory (RAM) device, such as a static RAM (SRAM) device, a magnetic RAM (MRAM) device, a resistive RAM (RRAM) device, a conductive-bridging RAM (CBRAM) device, etc.), a logic device (e.g., an AND, OR, NAND, or NOR gate), or any other suitable circuit element. Multiple ones of these devices may be combined on a single die **1502**. For example, a memory array formed by multiple memory devices may be formed on a same die **1502** as a processing device (e.g., the

processing device **1802** of FIG. **61**) or other logic that is configured to store information in the memory devices or execute instructions stored in the memory array.

(89) FIG. **59** is a side, cross-sectional view of an IC device **1600** that may be included in a microelectronic structure **100** and/or a microelectronic assembly **150**. For example, an IC device **1600** may be included in a microelectronic structure **100**/microelectronic assembly **150** as (or part of) a bridge component **110** and/or a microelectronic component **130**. An IC device **1600** may be part of a die **1502** (e.g., as discussed above with reference to FIG. **58**). One or more of the IC devices **1600** may be included in one or more dies **1502** (FIG. **58**). The IC device **1600** may be formed on a substrate **1602** (e.g., the wafer **1500** of FIG. **58**) and may be included in a die (e.g., the die **1502** of FIG. **58**). The substrate **1602** may be a semiconductor substrate composed of semiconductor material systems including, for example, n-type or p-type materials systems (or a combination of both). The substrate **1602** may include, for example, a crystalline substrate formed using a bulk silicon or a silicon-on-insulator (SOI) substructure. In some embodiments, the substrate **1602** may be formed using alternative materials, which may or may not be combined with silicon, that include but are not limited to germanium, indium antimonide, lead telluride, indium arsenide, indium phosphide, gallium arsenide, or gallium antimonide. Further materials classified as group II-VI, III-V, or IV may also be used to form the substrate **1602**. Although a few examples of materials from which the substrate **1602** may be formed are described here, any material that may serve as a foundation for an IC device **1600** may be used. The substrate **1602** may be part of a singulated die (e.g., the dies **1502** of FIG. **58**) or a wafer (e.g., the wafer **1500** of FIG. **58**).

(90) The IC device **1600** may include one or more device layers **1604** disposed on the substrate **1602**. The device layer **1604** may include features of one or more transistors **1640** (e.g., metal oxide semiconductor field-effect transistors (MOSFETs)) formed on the substrate **1602**. The device layer **1604** may include, for example, one or more source and/or drain (S/D) regions **1620**, a gate **1622** to control current flow in the transistors **1640** between the S/D regions **1620**, and one or more S/D contacts **1624** to route electrical signals to/from the S/D regions **1620**. The transistors **1640** may include additional features not depicted for the sake of clarity, such as device isolation regions, gate contacts, and the like. The transistors **1640** are not limited to the type and configuration depicted in FIG. **59** and may include a wide variety of other types and configurations such as, for example, planar transistors, non-planar transistors, or a combination of both. Planar transistors may include bipolar junction transistors (BJT), heterojunction bipolar transistors (HBT), or high-electron-mobility transistors (HEMT). Non-planar transistors may include FinFET transistors, such as double-gate transistors or tri-gate transistors, and wrap-around or all-around gate transistors, such as nanoribbon and nanowire transistors.

(91) Each transistor **1640** may include a gate **1622** formed of at least two layers, a gate dielectric and a gate electrode. The gate dielectric may include one layer or a stack of layers. The one or more layers may include silicon oxide, silicon dioxide, silicon carbide, and/or a high-k dielectric material. The high-k dielectric material may include elements such as hafnium, silicon, oxygen, titanium, tantalum, lanthanum, aluminum, zirconium, barium, strontium, yttrium, lead, scandium, niobium, and zinc. Examples of high-k materials that may be used in the gate dielectric include, but are not limited to, hafnium oxide, hafnium silicon oxide, lanthanum oxide, lanthanum aluminum oxide, zirconium oxide, zirconium silicon oxide, tantalum oxide, titanium oxide, barium strontium titanium oxide, barium titanium oxide, strontium titanium oxide, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, and lead zinc niobate. In some embodiments, an annealing process may be carried out on the gate dielectric to improve its quality when a high-k material is used.

(92) The gate electrode may be formed on the gate dielectric and may include at least one p-type work function metal or n-type work function metal, depending on whether the transistor **1640** is to be a p-type metal oxide semiconductor (PMOS) or an n-type metal oxide semiconductor (NMOS) transistor. In some implementations, the gate electrode may consist of a stack of two or more metal layers, where one or more metal layers are work function metal layers and at least one metal layer

is a fill metal layer. Further metal layers may be included for other purposes, such as a barrier layer. For a PMOS transistor, metals that may be used for the gate electrode include, but are not limited to, ruthenium, palladium, platinum, cobalt, nickel, conductive metal oxides (e.g., ruthenium oxide), and any of the metals discussed below with reference to an NMOS transistor (e.g., for work function tuning). For an NMOS transistor, metals that may be used for the gate electrode include, but are not limited to, hafnium, zirconium, titanium, tantalum, aluminum, alloys of these metals, carbides of these metals (e.g., hafnium carbide, zirconium carbide, titanium carbide, tantalum carbide, and aluminum carbide), and any of the metals discussed above with reference to a PMOS transistor (e.g., for work function tuning).

(93) In some embodiments, when viewed as a cross-section of the transistor **1640** along the source-channel-drain direction, the gate electrode may consist of a U-shaped structure that includes a bottom portion substantially parallel to the surface of the substrate and two sidewall portions that are substantially perpendicular to the top surface of the substrate. In other embodiments, at least one of the metal layers that form the gate electrode may simply be a planar layer that is substantially parallel to the top surface of the substrate and does not include sidewall portions substantially perpendicular to the top surface of the substrate. In other embodiments, the gate electrode may consist of a combination of U-shaped structures and planar, non-U-shaped structures. For example, the gate electrode may consist of one or more U-shaped metal layers formed atop one or more planar, non-U-shaped layers.

(94) In some embodiments, a pair of sidewall spacers may be formed on opposing sides of the gate stack to bracket the gate stack. The sidewall spacers may be formed from materials such as silicon nitride, silicon oxide, silicon carbide, silicon nitride doped with carbon, and silicon oxynitride. Processes for forming sidewall spacers are well known in the art and generally include deposition and etching process steps. In some embodiments, a plurality of spacer pairs may be used; for instance, two pairs, three pairs, or four pairs of sidewall spacers may be formed on opposing sides of the gate stack.

(95) The S/D regions **1620** may be formed within the substrate **1602** adjacent to the gate **1622** of each transistor **1640**. The S/D regions **1620** may be formed using an implantation/diffusion process or an etching/deposition process, for example. In the former process, dopants such as boron, aluminum, antimony, phosphorous, or arsenic may be ion-implanted into the substrate **1602** to form the S/D regions **1620**. An annealing process that activates the dopants and causes them to diffuse farther into the substrate **1602** may follow the ion-implantation process. In the latter process, the substrate **1602** may first be etched to form recesses at the locations of the S/D regions **1620**. An epitaxial deposition process may then be carried out to fill the recesses with material that is used to fabricate the S/D regions **1620**. In some implementations, the S/D regions **1620** may be fabricated using a silicon alloy such as silicon germanium or silicon carbide. In some embodiments, the epitaxially deposited silicon alloy may be doped in situ with dopants such as boron, arsenic, or phosphorous. In some embodiments, the S/D regions **1620** may be formed using one or more alternate semiconductor materials such as germanium or a group III-V material or alloy. In further embodiments, one or more layers of metal and/or metal alloys may be used to form the S/D regions **1620**.

(96) Electrical signals, such as power and/or input/output (I/O) signals, may be routed to and/or from the devices (e.g., the transistors **1640**) of the device layer **1604** through one or more interconnect layers disposed on the device layer **1604** (illustrated in FIG. **59** as interconnect layers **1606-1610**). For example, electrically conductive features of the device layer **1604** (e.g., the gate **1622** and the S/D contacts **1624**) may be electrically coupled with the interconnect structures **1628** of the interconnect layers **1606-1610**. The one or more interconnect layers **1606-1610** may form a metallization stack (also referred to as an “ILD stack”) **1619** of the IC device **1600**. In some embodiments, an IC device **1600** may be a “passive” device in that it includes no active components (e.g., transistors), while in other embodiments, a die **1502** may be an “active” die in

that it includes active components.

(97) The interconnect structures **1628** may be arranged within the interconnect layers **1606-1610** to route electrical signals according to a wide variety of designs (in particular, the arrangement is not limited to the particular configuration of interconnect structures **1628** depicted in FIG. 59). Although a particular number of interconnect layers **1606-1610** is depicted in FIG. 59, embodiments of the present disclosure include IC devices having more or fewer interconnect layers than depicted.

(98) In some embodiments, the interconnect structures **1628** may include lines **1628a** and/or vias **1628b** filled with an electrically conductive material such as a metal. The lines **1628a** may be arranged to route electrical signals in a direction of a plane that is substantially parallel with a surface of the substrate **1602** upon which the device layer **1604** is formed. For example, the lines **1628a** may route electrical signals in a direction in and out of the page from the perspective of FIG. 59. The vias **1628b** may be arranged to route electrical signals in a direction of a plane that is substantially perpendicular to the surface of the substrate **1602** upon which the device layer **1604** is formed. In some embodiments, the vias **1628b** may electrically couple lines **1628a** of different interconnect layers **1606-1610** together.

(99) The interconnect layers **1606-1610** may include a dielectric material **1626** disposed between the interconnect structures **1628**, as shown in FIG. 59. In some embodiments, the dielectric material **1626** disposed between the interconnect structures **1628** in different ones of the interconnect layers **1606-1610** may have different compositions; in other embodiments, the composition of the dielectric material **1626** between different interconnect layers **1606-1610** may be the same.

(100) A first interconnect layer **1606** may be formed above the device layer **1604**. In some embodiments, the first interconnect layer **1606** may include lines **1628a** and/or vias **1628b**, as shown. The lines **1628a** of the first interconnect layer **1606** may be coupled with contacts (e.g., the S/D contacts **1624**) of the device layer **1604**.

(101) A second interconnect layer **1608** may be formed above the first interconnect layer **1606**. In some embodiments, the second interconnect layer **1608** may include vias **1628b** to couple the lines **1628a** of the second interconnect layer **1608** with the lines **1628a** of the first interconnect layer **1606**. Although the lines **1628a** and the vias **1628b** are structurally delineated with a line within each interconnect layer (e.g., within the second interconnect layer **1608**) for the sake of clarity, the lines **1628a** and the vias **1628b** may be structurally and/or materially contiguous (e.g., simultaneously filled during a dual-damascene process) in some embodiments.

(102) A third interconnect layer **1610** (and additional interconnect layers, as desired) may be formed in succession on the second interconnect layer **1608** according to similar techniques and configurations described in connection with the second interconnect layer **1608** or the first interconnect layer **1606**. In some embodiments, the interconnect layers that are “higher up” in the metallization stack **1619** in the IC device **1600** (i.e., farther away from the device layer **1604**) may be thicker.

(103) The IC device **1600** may include a surface insulation material **1634** (e.g., polyimide or similar material) and one or more conductive contacts **1636** formed on the interconnect layers **1606-1610**. In FIG. 59, the conductive contacts **1636** are illustrated as taking the form of bond pads. The conductive contacts **1636** may be electrically coupled with the interconnect structures **1628** and configured to route the electrical signals of the transistor(s) **1640** to other external devices. For example, solder bonds may be formed on the one or more conductive contacts **1636** to mechanically and/or electrically couple a chip including the IC device **1600** with another component (e.g., a circuit board). The IC device **1600** may include additional or alternate structures to route the electrical signals from the interconnect layers **1606-1610**; for example, the conductive contacts **1636** may include other analogous features (e.g., posts) that route the electrical signals to external components.

(104) FIG. 60 is a side, cross-sectional view of an IC device assembly **1700** that may include one or more microelectronic structures **100** and/or microelectronic assemblies **150**, in accordance with any of the embodiments disclosed herein. The IC device assembly **1700** includes a number of components disposed on a circuit board **1702** (which may be, e.g., a motherboard). The IC device assembly **1700** includes components disposed on a first face **1740** of the circuit board **1702** and an opposing second face **1742** of the circuit board **1702**; generally, components may be disposed on one or both faces **1740** and **1742**. Any of the IC packages discussed below with reference to the IC device assembly **1700** may take the form of any of the embodiments of the microelectronic assemblies **150** discussed herein, or may otherwise include any of the microelectronic structures **100** disclosed herein.

(105) In some embodiments, the circuit board **1702** may be a PCB including multiple metal layers separated from one another by layers of dielectric material and interconnected by electrically conductive vias. Any one or more of the metal layers may be formed in a desired circuit pattern to route electrical signals (optionally in conjunction with other metal layers) between the components coupled to the circuit board **1702**. In other embodiments, the circuit board **1702** may be a non-PCB substrate.

(106) The IC device assembly **1700** illustrated in FIG. 60 includes a package-on-interposer structure **1736** coupled to the first face **1740** of the circuit board **1702** by coupling components **1716**. The coupling components **1716** may electrically and mechanically couple the package-on-interposer structure **1736** to the circuit board **1702**, and may include solder balls (as shown in FIG. 60), male and female portions of a socket, an adhesive, an underfill material, and/or any other suitable electrical and/or mechanical coupling structure.

(107) The package-on-interposer structure **1736** may include an IC package **1720** coupled to a package interposer **1704** by coupling components **1718**. The coupling components **1718** may take any suitable form for the application, such as the forms discussed above with reference to the coupling components **1716**. Although a single IC package **1720** is shown in FIG. 60, multiple IC packages may be coupled to the package interposer **1704**; indeed, additional interposers may be coupled to the package interposer **1704**. The package interposer **1704** may provide an intervening substrate used to bridge the circuit board **1702** and the IC package **1720**. The IC package **1720** may be or include, for example, a die (the die **1502** of FIG. 58), an IC device (e.g., the IC device **1600** of FIG. 59), or any other suitable component. Generally, the package interposer **1704** may spread a connection to a wider pitch or reroute a connection to a different connection. For example, the package interposer **1704** may couple the IC package **1720** (e.g., a die) to a set of ball grid array (BGA) conductive contacts of the coupling components **1716** for coupling to the circuit board **1702**. In the embodiment illustrated in FIG. 60, the IC package **1720** and the circuit board **1702** are attached to opposing sides of the package interposer **1704**; in other embodiments, the IC package **1720** and the circuit board **1702** may be attached to a same side of the package interposer **1704**. In some embodiments, three or more components may be interconnected by way of the package interposer **1704**.

(108) In some embodiments, the package interposer **1704** may be formed as a PCB, including multiple metal layers separated from one another by layers of dielectric material and interconnected by electrically conductive vias. In some embodiments, the package interposer **1704** may be formed of an epoxy resin, a fiberglass-reinforced epoxy resin, an epoxy resin with inorganic fillers, a ceramic material, or a polymer material such as polyimide. In some embodiments, the package interposer **1704** may be formed of alternate rigid or flexible materials that may include the same materials described above for use in a semiconductor substrate, such as silicon, germanium, and other group III-V and group IV materials. The package interposer **1704** may include metal lines **1710** and vias **1708**, including but not limited to through-silicon vias (TSVs) **1706**. The package interposer **1704** may further include embedded devices **1714**, including both passive and active devices. Such devices may include, but are not limited to, capacitors, decoupling capacitors,

resistors, inductors, fuses, diodes, transformers, sensors, electrostatic discharge (ESD) devices, and memory devices. More complex devices such as radio frequency devices, power amplifiers, power management devices, antennas, arrays, sensors, and microelectromechanical systems (MEMS) devices may also be formed on the package interposer **1704**. The package-on-interposer structure **1736** may take the form of any of the package-on-interposer structures known in the art. In some embodiments, the package interposer **1704** may include one or more microelectronic structures **100** and/or microelectronic assemblies **150**.

(109) The IC device assembly **1700** may include an IC package **1724** coupled to the first face **1740** of the circuit board **1702** by coupling components **1722**. The coupling components **1722** may take the form of any of the embodiments discussed above with reference to the coupling components **1716**, and the IC package **1724** may take the form of any of the embodiments discussed above with reference to the IC package **1720**.

(110) The IC device assembly **1700** illustrated in FIG. **60** includes a package-on-package structure **1734** coupled to the second face **1742** of the circuit board **1702** by coupling components **1728**. The package-on-package structure **1734** may include an IC package **1726** and an IC package **1732** coupled together by coupling components **1730** such that the IC package **1726** is disposed between the circuit board **1702** and the IC package **1732**. The coupling components **1728** and **1730** may take the form of any of the embodiments of the coupling components **1716** discussed above, and the IC packages **1726** and **1732** may take the form of any of the embodiments of the IC package **1720** discussed above. The package-on-package structure **1734** may be configured in accordance with any of the package-on-package structures known in the art.

(111) FIG. **61** is a block diagram of an example electrical device **1800** that may include one or more microelectronic structures **100** and/or microelectronic assemblies **150** in accordance with any of the embodiments disclosed herein. For example, any suitable ones of the components of the electrical device **1800** may include one or more of the microelectronic structures **100**, microelectronic assemblies **150**, IC device assemblies **1700**, IC devices **1600**, or dies **1502** disclosed herein. A number of components are illustrated in FIG. **61** as included in the electrical device **1800**, but any one or more of these components may be omitted or duplicated, as suitable for the application. In some embodiments, some or all of the components included in the electrical device **1800** may be attached to one or more motherboards. In some embodiments, some or all of these components are fabricated onto a single system-on-a-chip (SoC) die.

(112) Additionally, in various embodiments, the electrical device **1800** may not include one or more of the components illustrated in FIG. **61**, but the electrical device **1800** may include interface circuitry for coupling to the one or more components. For example, the electrical device **1800** may not include a display device **1806**, but may include display device interface circuitry (e.g., a connector and driver circuitry) to which a display device **1806** may be coupled. In another set of examples, the electrical device **1800** may not include an audio input device **1824** or an audio output device **1808**, but may include audio input or output device interface circuitry (e.g., connectors and supporting circuitry) to which an audio input device **1824** or audio output device **1808** may be coupled.

(113) The electrical device **1800** may include a processing device **1802** (e.g., one or more processing devices). As used herein, the term “processing device” or “processor” may refer to any device or portion of a device that processes electronic data from registers and/or memory to transform that electronic data into other electronic data that may be stored in registers and/or memory. The processing device **1802** may include one or more digital signal processors (DSPs), application-specific integrated circuits (ASICs), central processing units (CPUs), graphics processing units (GPUs), cryptoprocessors (specialized processors that execute cryptographic algorithms within hardware), server processors, or any other suitable processing devices. The electrical device **1800** may include a memory **1804**, which may itself include one or more memory devices such as volatile memory (e.g., dynamic random access memory (DRAM)), nonvolatile

memory (e.g., read-only memory (ROM)), flash memory, solid state memory, and/or a hard drive. In some embodiments, the memory **1804** may include memory that shares a die with the processing device **1802**. This memory may be used as cache memory and may include embedded dynamic random access memory (eDRAM) or spin transfer torque magnetic random access memory (STT-MRAM).

(114) In some embodiments, the electrical device **1800** may include a communication chip **1812** (e.g., one or more communication chips). For example, the communication chip **1812** may be configured for managing wireless communications for the transfer of data to and from the electrical device **1800**. The term “wireless” and its derivatives may be used to describe circuits, devices, systems, methods, techniques, communications channels, etc., that may communicate data through the use of modulated electromagnetic radiation through a nonsolid medium. The term does not imply that the associated devices do not contain any wires, although in some embodiments they might not.

(115) The communication chip **1812** may implement any of a number of wireless standards or protocols, including but not limited to Institute for Electrical and Electronic Engineers (IEEE) standards including Wi-Fi (IEEE 802.11 family), IEEE 802.16 standards (e.g., IEEE 802.16-2005 Amendment), Long-Term Evolution (LTE) project along with any amendments, updates, and/or revisions (e.g., advanced LTE project, ultra mobile broadband (UMB) project (also referred to as “3GPP2”), etc.). IEEE 802.16 compatible Broadband Wireless Access (BWA) networks are generally referred to as WiMAX networks, an acronym that stands for Worldwide Interoperability for Microwave Access, which is a certification mark for products that pass conformity and interoperability tests for the IEEE 802.16 standards. The communication chip **1812** may operate in accordance with a Global System for Mobile Communication (GSM), General Packet Radio Service (GPRS), Universal Mobile Telecommunications System (UMTS), High Speed Packet Access (HSPA), Evolved HSPA (E-HSPA), or LTE network. The communication chip **1812** may operate in accordance with Enhanced Data for GSM Evolution (EDGE), GSM EDGE Radio Access Network (GERAN), Universal Terrestrial Radio Access Network (UTRAN), or Evolved UTRAN (E-UTRAN). The communication chip **1812** may operate in accordance with Code Division Multiple Access (CDMA), Time Division Multiple Access (TDMA), Digital Enhanced Cordless Telecommunications (DECT), Evolution-Data Optimized (EV-DO), and derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The communication chip **1812** may operate in accordance with other wireless protocols in other embodiments. The electrical device **1800** may include an antenna **1822** to facilitate wireless communications and/or to receive other wireless communications (such as AM or FM radio transmissions).

(116) In some embodiments, the communication chip **1812** may manage wired communications, such as electrical, optical, or any other suitable communication protocols (e.g., the Ethernet). As noted above, the communication chip **1812** may include multiple communication chips. For instance, a first communication chip **1812** may be dedicated to shorter-range wireless communications such as Wi-Fi or Bluetooth, and a second communication chip **1812** may be dedicated to longer-range wireless communications such as global positioning system (GPS), EDGE, GPRS, CDMA, WiMAX, LTE, EV-DO, or others. In some embodiments, a first communication chip **1812** may be dedicated to wireless communications, and a second communication chip **1812** may be dedicated to wired communications.

(117) The electrical device **1800** may include battery/power circuitry **1814**. The battery/power circuitry **1814** may include one or more energy storage devices (e.g., batteries or capacitors) and/or circuitry for coupling components of the electrical device **1800** to an energy source separate from the electrical device **1800** (e.g., AC line power).

(118) The electrical device **1800** may include a display device **1806** (or corresponding interface circuitry, as discussed above). The display device **1806** may include any visual indicators, such as a heads-up display, a computer monitor, a projector, a touchscreen display, a liquid crystal display

(LCD), a light-emitting diode display, or a flat panel display.

(119) The electrical device **1800** may include an audio output device **1808** (or corresponding interface circuitry, as discussed above). The audio output device **1808** may include any device that generates an audible indicator, such as speakers, headsets, or earbuds.

(120) The electrical device **1800** may include an audio input device **1824** (or corresponding interface circuitry, as discussed above). The audio input device **1824** may include any device that generates a signal representative of a sound, such as microphones, microphone arrays, or digital instruments (e.g., instruments having a musical instrument digital interface (MIDI) output).

(121) The electrical device **1800** may include a GPS device **1818** (or corresponding interface circuitry, as discussed above). The GPS device **1818** may be in communication with a satellite-based system and may receive a location of the electrical device **1800**, as known in the art.

(122) The electrical device **1800** may include an other output device **1810** (or corresponding interface circuitry, as discussed above). Examples of the other output device **1810** may include an audio codec, a video codec, a printer, a wired or wireless transmitter for providing information to other devices, or an additional storage device.

(123) The electrical device **1800** may include an other input device **1820** (or corresponding interface circuitry, as discussed above). Examples of the other input device **1820** may include an accelerometer, a gyroscope, a compass, an image capture device, a keyboard, a cursor control device such as a mouse, a stylus, a touchpad, a bar code reader, a Quick Response (QR) code reader, any sensor, or a radio frequency identification (RFID) reader.

(124) The electrical device **1800** may have any desired form factor, such as a handheld or mobile electrical device (e.g., a cell phone, a smart phone, a mobile internet device, a music player, a tablet computer, a laptop computer, a netbook computer, an ultrabook computer, a personal digital assistant (PDA), an ultra mobile personal computer, etc.), a desktop electrical device, a server device or other networked computing component, a printer, a scanner, a monitor, a set-top box, an entertainment control unit, a vehicle control unit, a digital camera, a digital video recorder, or a wearable electrical device. In some embodiments, the electrical device **1800** may be any other electronic device that processes data.

(125) The following paragraphs provide various examples of the embodiments disclosed herein.

(126) Example A1 is a microelectronic structure, including: a substrate including a surface insulation material at a face of the substrate; a cavity in the substrate, wherein the cavity extends at least through the surface insulation material; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component.

(127) Example A2 includes the subject matter of Example A1, and further specifies that the substrate includes an organic dielectric material.

(128) Example A3 includes the subject matter of any of Examples A1-2, and further specifies that the substrate includes a conductive contact at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(129) Example A4 includes the subject matter of Example A3, and further includes: solder on the conductive contact of the substrate.

(130) Example A5 includes the subject matter of any of Examples A3-4, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(131) Example A6 includes the subject matter of Example A5, and further specifies that the second conductive contact is a second-level interconnect contact.

- (132) Example A7 includes the subject matter of any of Examples A1-6, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.
- (133) Example A8 includes the subject matter of any of Examples A1-7, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.
- (134) Example A9 includes the subject matter of Example A8, and further specifies that the bridge component is coupled to the dielectric material.
- (135) Example A10 includes the subject matter of Example A9, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.
- (136) Example A11 includes the subject matter of any of Examples A8-10, and further specifies that the bottom of the cavity is coplanar with a bottom of a conductive contact of the substrate at the face of the substrate.
- (137) Example A12 includes the subject matter of any of Examples A1-7, and further specifies that a metal is at a bottom of the cavity.
- (138) Example A13 includes the subject matter of Example A12, and further specifies that a bottom of the metal is coplanar with a bottom of the surface insulation material.
- (139) Example A14 includes the subject matter of any of Examples A12-13, and further specifies that the metal extends onto the surface insulation material at side faces of the cavity.
- (140) Example A15 includes the subject matter of any of Examples A12-14, and further specifies that the metal has a thickness that is less than a thickness of a conductive contact of the substrate at the face of the substrate.
- (141) Example A16 includes the subject matter of Example A15, and further specifies that the thickness of the metal is less than 5 microns.
- (142) Example A17 includes the subject matter of any of Examples A12-13, and further specifies that a top of the metal is coplanar with a top of a conductive contact of the substrate at the face of the substrate.
- (143) Example A18 includes the subject matter of Example A17, and further specifies that a thickness of the metal is greater than 5 microns.
- (144) Example A19 includes the subject matter of any of Examples A12-18, and further specifies that the bridge component is coupled to the metal.
- (145) Example A20 includes the subject matter of Example A19, and further specifies that the bridge component is coupled to the metal by an adhesive.
- (146) Example A21 includes the subject matter of Example A20, and further specifies that the adhesive includes a snap-curable adhesive.
- (147) Example A22 includes the subject matter of any of Examples A12-21, and further specifies that the metal includes nickel, palladium, and gold.
- (148) Example A23 includes the subject matter of any of Examples A12-21, and further specifies that the metal includes aluminum.
- (149) Example A24 includes the subject matter of any of Examples A12-21, and further specifies that the metal includes copper.
- (150) Example A25 includes the subject matter of any of Examples A1-24, and further specifies that a bottom of the cavity has an undulating surface.
- (151) Example A26 includes the subject matter of Example A25, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.
- (152) Example A27 includes the subject matter of any of Examples A25, and further specifies that the undulations have an amplitude that is less than 1 micron.
- (153) Example A28 includes the subject matter of any of Examples A1-27, and further specifies that the surface insulation material has a thickness between 10 microns and 30 microns.
- (154) Example A29 includes the subject matter of any of Examples A1-28, and further specifies that the bridge component includes a semiconductor material.
- (155) Example A30 includes the subject matter of any of Examples A1-29, and further specifies

that the bridge component has a thickness that is less than 100 microns.

(156) Example A31 is a microelectronic assembly, including: a substrate; a cavity at a face of the substrate; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(157) Example A32 includes the subject matter of Example A31, and further specifies that the substrate includes an organic dielectric material.

(158) Example A33 includes the subject matter of any of Examples A31-32, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(159) Example A34 includes the subject matter of Example A33, and further includes: solder on the conductive contact of the substrate.

(160) Example A35 includes the subject matter of any of Examples A33-34, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(161) Example A36 includes the subject matter of Example A35, and further specifies that the second conductive contact is a second-level interconnect contact.

(162) Example A37 includes the subject matter of any of Examples A31-36, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(163) Example A38 includes the subject matter of any of Examples A31-37, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(164) Example A39 includes the subject matter of Example A38, and further specifies that the bridge component is coupled to the dielectric material.

(165) Example A40 includes the subject matter of Example A39, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.

(166) Example A41 includes the subject matter of any of Examples A38-40, and further specifies that the bottom of the cavity is coplanar with a bottom of a conductive contact of the substrate at the face of the substrate.

(167) Example A42 includes the subject matter of any of Examples A31-37, and further specifies that a metal is at a bottom of the cavity.

(168) Example A43 includes the subject matter of Example A42, and further specifies that a bottom of the metal is coplanar with a bottom of surface insulation material at the face of the substrate.

(169) Example A44 includes the subject matter of any of Examples A42-43, and further specifies that the metal extends onto surface insulation material at side faces of the cavity.

(170) Example A45 includes the subject matter of any of Examples A42-44, and further specifies that the metal has a thickness that is less than a thickness of a conductive contact of the substrate at the face of the substrate.

(171) Example A46 includes the subject matter of Example A45, and further specifies that the thickness of the metal is less than 5 microns.

(172) Example A47 includes the subject matter of any of Examples A42-43, and further specifies that a top of the metal is coplanar with a top of a conductive contact of the substrate at the face of the substrate.

(173) Example A48 includes the subject matter of Example A47, and further specifies that a thickness of the metal is greater than 5 microns.

(174) Example A49 includes the subject matter of any of Examples A42-48, and further specifies that the bridge component is coupled to the metal.

(175) Example A50 includes the subject matter of Example A49, and further specifies that the bridge component is coupled to the metal by an adhesive.

(176) Example A51 includes the subject matter of Example A50, and further specifies that the adhesive includes a snap-curable adhesive.

(177) Example A52 includes the subject matter of any of Examples A42-51, and further specifies that the metal includes nickel, palladium, and gold.

(178) Example A53 includes the subject matter of any of Examples A42-51, and further specifies that the metal includes aluminum.

(179) Example A54 includes the subject matter of any of Examples A42-51, and further specifies that the metal includes copper.

(180) Example A55 includes the subject matter of any of Examples A31-54, and further specifies that a bottom of the cavity has an undulating surface.

(181) Example A56 includes the subject matter of Example A55, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(182) Example A57 includes the subject matter of Example A55, and further specifies that the undulations have an amplitude that is less than 1 micron.

(183) Example A58 includes the subject matter of any of Examples A31-57, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(184) Example A59 includes the subject matter of any of Examples A31-58, and further specifies that the bridge component includes a semiconductor material.

(185) Example A60 includes the subject matter of any of Examples A31-59, and further specifies that the bridge component has a thickness that is less than 100 microns.

(186) Example A61 includes the subject matter of any of Examples A31-60, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(187) Example A62 includes the subject matter of any of Examples A31-61, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(188) Example A63 includes the subject matter of any of Examples A31-62, and further specifies that the microelectronic component includes a die.

(189) Example A64 includes the subject matter of any of Examples A31-63, and further includes: a fill compound between the microelectronic component and the substrate.

(190) Example A65 includes the subject matter of Example A64, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(191) Example A66 includes the subject matter of any of Examples A31-65, and further specifies

that the microelectronic component includes a transistor.

(192) Example A67 includes the subject matter of any of Examples A31-66, and further specifies that the microelectronic component includes a memory device.

(193) Example A68 includes the subject matter of any of Examples A31-67, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(194) Example A69 includes the subject matter of any of Examples A31-68, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(195) Example A70 includes the subject matter of Example A69, and further specifies that the surface finish further includes palladium and gold.

(196) Example A71 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity at a face of the substrate; a bridge component in the cavity; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the substrate, and some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the bridge component.

(197) Example A72 includes the subject matter of Example A71, and further specifies that the substrate includes an organic dielectric material.

(198) Example A73 includes the subject matter of any of Examples A71-72, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(199) Example A74 includes the subject matter of Example A73, and further includes: solder on the conductive contact of the substrate.

(200) Example A75 includes the subject matter of any of Examples A73-74, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(201) Example A76 includes the subject matter of Example A75, and further specifies that the second conductive contact is a second-level interconnect contact.

(202) Example A77 includes the subject matter of any of Examples A71-76, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(203) Example A78 includes the subject matter of any of Examples A71-77, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(204) Example A79 includes the subject matter of Example A78, and further specifies that the bridge component is coupled to the dielectric material.

(205) Example A80 includes the subject matter of Example A79, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.

(206) Example A81 includes the subject matter of any of Examples A78-80, and further specifies that the bottom of the cavity is coplanar with a bottom of a conductive contact of the substrate at the face of the substrate.

(207) Example A82 includes the subject matter of any of Examples A71-77, and further specifies that a metal is at a bottom of the cavity.

(208) Example A83 includes the subject matter of Example A82, and further specifies that a bottom of the metal is coplanar with a bottom of surface insulation material at the face of the substrate.

(209) Example A84 includes the subject matter of any of Examples A82-83, and further specifies that the metal extends onto surface insulation material at side faces of the cavity.

(210) Example A85 includes the subject matter of any of Examples A82-84, and further specifies that the metal has a thickness that is less than a thickness of a conductive contact of the substrate at the face of the substrate.

(211) Example A86 includes the subject matter of Example A85, and further specifies that the thickness of the metal is less than 5 microns.

(212) Example A87 includes the subject matter of any of Examples A82-83, and further specifies that a top of the metal is coplanar with a top of a conductive contact of the substrate at the face of the substrate.

(213) Example A88 includes the subject matter of Example A87, and further specifies that a thickness of the metal is greater than 5 microns.

(214) Example A89 includes the subject matter of any of Examples A82-88, and further specifies that the bridge component is coupled to the metal.

(215) Example A90 includes the subject matter of Example A89, and further specifies that the bridge component is coupled to the metal by an adhesive.

(216) Example A91 includes the subject matter of Example A90, and further specifies that the adhesive includes a snap-curable adhesive.

(217) Example A92 includes the subject matter of any of Examples A82-91, and further specifies that the metal includes nickel, palladium, and gold.

(218) Example A93 includes the subject matter of any of Examples A82-91, and further specifies that the metal includes aluminum.

(219) Example A94 includes the subject matter of any of Examples A82-91, and further specifies that the metal includes copper.

(220) Example A95 includes the subject matter of any of Examples A71-94, and further specifies that a bottom of the cavity has an undulating surface.

(221) Example A96 includes the subject matter of Example A95, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(222) Example A97 includes the subject matter of Example A95, and further specifies that the undulations have an amplitude that is less than 1 micron.

(223) Example A98 includes the subject matter of any of Examples A71-97, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(224) Example A99 includes the subject matter of any of Examples A71-98, and further specifies that the bridge component includes a semiconductor material.

(225) Example A100 includes the subject matter of any of Examples A71-99, and further specifies that the bridge component has a thickness that is less than 100 microns.

(226) Example A101 includes the subject matter of any of Examples A71-100, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(227) Example A102 includes the subject matter of any of Examples A71-101, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(228) Example A103 includes the subject matter of any of Examples A71-102, and further specifies that the microelectronic component includes a die.

(229) Example A104 includes the subject matter of any of Examples A71-103, and further includes: a fill compound between the microelectronic component and the substrate.

(230) Example A105 includes the subject matter of Example A104, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(231) Example A106 includes the subject matter of any of Examples A71-105, and further specifies that the microelectronic component includes a transistor.

(232) Example A107 includes the subject matter of any of Examples A71-106, and further specifies that the microelectronic component includes a memory device.

(233) Example A108 includes the subject matter of any of Examples A71-107, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(234) Example A109 includes the subject matter of any of Examples A71-108, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(235) Example A110 includes the subject matter of Example A109, and further specifies that the surface finish further includes palladium and gold.

(236) Example A111 includes the subject matter of any of Examples A71-110, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(237) Example A112 includes the subject matter of any of Examples A71-111, and further specifies that the circuit board is a motherboard.

(238) Example A113 includes the subject matter of any of Examples A71-112, and further includes: a display communicatively coupled to the circuit board.

(239) Example A114 includes the subject matter of Example A113, and further specifies that the display includes a touchscreen display.

(240) Example A115 includes the subject matter of any of Examples A71-114, and further includes: a housing around the circuit board and the microelectronic assembly.

(241) Example A116 is a method of manufacturing a microelectronic structure, including any of the methods disclosed herein.

(242) Example A117 is a method of manufacturing a microelectronic assembly, including any of the methods disclosed herein.

(243) Example B1 is a microelectronic structure, including: a substrate including a first layer, a last layer, and one or more interior layers between the first layer and the last layer; a cavity in a face of the substrate, wherein the face of the substrate is proximate to the last layer, and the cavity extends through and past the last layer; a metal at a bottom of the cavity; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component.

(244) Example B2 includes the subject matter of Example B1, and further specifies that the substrate includes an organic dielectric material.

(245) Example B3 includes the subject matter of any of Examples B1-2, and further specifies that the substrate includes a conductive contact at the face of the substrate, the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(246) Example B4 includes the subject matter of Example B3, and further includes: solder on the conductive contact of the substrate.

(247) Example B5 includes the subject matter of any of Examples B3-4, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate

opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(248) Example B6 includes the subject matter of Example B5, and further specifies that the second conductive contact is a second-level interconnect contact.

(249) Example B7 includes the subject matter of any of Examples B1-6, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(250) Example B8 includes the subject matter of any of Examples B1-7, and further specifies that a metal at a bottom of the cavity is adjacent to a metal line of an interior metal layer of the substrate.

(251) Example B9 includes the subject matter of Example B8, and further specifies that the metal line includes copper.

(252) Example B10 includes the subject matter of Example B9, and further specifies that the metal is different from copper.

(253) Example B11 includes the subject matter of any of Examples B8-10, and further specifies that the metal has a thickness that is less than a thickness of the metal line.

(254) Example B12 includes the subject matter of any of Examples B1-11, and further specifies that the metal extends onto side faces of the cavity.

(255) Example B13 includes the subject matter of any of Examples B1-11, and further specifies that the metal does not extend onto side faces of the cavity.

(256) Example B14 includes the subject matter of any of Examples B1-13, and further specifies that the thickness of the metal is less than 1 micron.

(257) Example B15 includes the subject matter of any of Examples B1-14, and further specifies that the bridge component is coupled to the metal.

(258) Example B16 includes the subject matter of any of Examples B1-15, and further includes: an adhesive between the bridge component and the metal.

(259) Example B17 includes the subject matter of Example B16, and further specifies that the adhesive includes a snap-curable adhesive.

(260) Example B18 includes the subject matter of any of Examples B16-17, and further specifies that the adhesive includes a UV-curable adhesive.

(261) Example B19 includes the subject matter of any of Examples B16-17, and further specifies that the adhesive includes a first adhesive region and a second adhesive region, and a material composition of the first adhesive region is different from a material composition of the second adhesive region.

(262) Example B20 includes the subject matter of Example B19, and further specifies that the first adhesive region is proximate to edges of the bridge component and the second adhesive region is proximate to an interior of the bridge component.

(263) Example B21 includes the subject matter of any of Examples B19-20, and further specifies that the second adhesive region includes a thermally curable adhesive and the first adhesive region includes a snap-curable adhesive.

(264) Example B22 includes the subject matter of any of Examples B16-21, and further specifies that the metal does not extend outside the region between the adhesive and the bottom of the cavity.

(265) Example B23 includes the subject matter of any of Examples B1-22, and further specifies that the metal includes aluminum.

(266) Example B24 includes the subject matter of any of Examples B1-23, and further specifies that the metal includes gold.

(267) Example B25 includes the subject matter of any of Examples B1-24, and further specifies that a diameter of an opening of the cavity is greater than a diameter of a bottom of the cavity by greater than 5 microns.

(268) Example B26 includes the subject matter of any of Examples B1-25, and further specifies that a bottom of the cavity has an undulating surface.

(269) Example B27 includes the subject matter of Example B26, and further specifies that the

undulations have an amplitude between 1 micron and 10 microns.

(270) Example B28 includes the subject matter of any of Examples B1-27, and further specifies that surface insulation material of the substrate has a thickness between 10 microns and 30 microns.

(271) Example B29 includes the subject matter of any of Examples B1-28, and further specifies that the bridge component includes a semiconductor material.

(272) Example B30 includes the subject matter of any of Examples B1-29, and further specifies that the bridge component has a thickness that is less than 100 microns.

(273) Example B31 is a microelectronic assembly, including: a substrate; a cavity in a face of the substrate, wherein the face of the substrate is proximate to a metallization layer of the substrate, and the cavity extends through and past the metallization layer; a metal at a bottom of the cavity; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(274) Example B32 includes the subject matter of Example B31, and further specifies that the substrate includes an organic dielectric material.

(275) Example B33 includes the subject matter of any of Examples B31-32, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(276) Example B34 includes the subject matter of Example B33, and further includes: solder on the conductive contact of the substrate.

(277) Example B35 includes the subject matter of any of Examples B33-34, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(278) Example B36 includes the subject matter of Example B35, and further specifies that the second conductive contact is a second-level interconnect contact.

(279) Example B37 includes the subject matter of any of Examples B31-36, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(280) Example B38 includes the subject matter of any of Examples B31-37, and further specifies that a metal at a bottom of the cavity is adjacent to a metal line of an interior metal layer of the substrate.

(281) Example B39 includes the subject matter of Example B38, and further specifies that the metal line includes copper.

(282) Example B40 includes the subject matter of Example B39, and further specifies that the metal is different from copper.

(283) Example B41 includes the subject matter of any of Examples B38-40, and further specifies that the metal has a thickness that is less than a thickness of the metal line.

(284) Example B42 includes the subject matter of any of Examples B31-41, and further specifies that the metal extends onto side faces of the cavity.

(285) Example B43 includes the subject matter of any of Examples B31-41, and further specifies that the metal does not extend onto side faces of the cavity.

(286) Example B44 includes the subject matter of any of Examples B31-43, and further specifies that the thickness of the metal is less than 1 micron.

(287) Example B45 includes the subject matter of any of Examples B31-44, and further specifies that the bridge component is coupled to the metal.

(288) Example B46 includes the subject matter of any of Examples B31-45, and further includes: an adhesive between the bridge component and the metal.

(289) Example B47 includes the subject matter of Example B46, and further specifies that the adhesive includes a snap-curable adhesive.

(290) Example B48 includes the subject matter of any of Examples B46-47, and further specifies that the adhesive includes a UV-curable adhesive.

(291) Example B49 includes the subject matter of any of Examples B46-47, and further specifies that the adhesive includes a first adhesive region and a second adhesive region, and a material composition of the first adhesive region is different from a material composition of the second adhesive region.

(292) Example B50 includes the subject matter of Example B49, and further specifies that the first adhesive region is proximate to edges of the bridge component and the second adhesive region is proximate to an interior of the bridge component.

(293) Example B51 includes the subject matter of any of Examples B49-50, and further specifies that the second adhesive region includes a thermally curable adhesive and the first adhesive region includes a snap-curable adhesive.

(294) Example B52 includes the subject matter of any of Examples B46-51, and further specifies that the metal does not extend outside the region between the adhesive and the bottom of the cavity.

(295) Example B53 includes the subject matter of any of Examples B31-52, and further specifies that the metal includes aluminum.

(296) Example B54 includes the subject matter of any of Examples B31-53, and further specifies that the metal includes gold.

(297) Example B55 includes the subject matter of any of Examples B31-54, and further specifies that a diameter of an opening of the cavity is greater than a diameter of a bottom of the cavity by greater than 5 microns.

(298) Example B56 includes the subject matter of any of Examples B31-55, and further specifies that a bottom of the cavity has an undulating surface.

(299) Example B57 includes the subject matter of any of Examples B56, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(300) Example B58 includes the subject matter of any of Examples B31-57, and further specifies that surface insulation material of the substrate has a thickness between 10 microns and 30 microns.

(301) Example B59 includes the subject matter of any of Examples B31-58, and further specifies that the bridge component includes a semiconductor material.

(302) Example B60 includes the subject matter of any of Examples B31-59, and further specifies that the bridge component has a thickness that is less than 100 microns.

(303) Example B61 includes the subject matter of any of Examples B31-60, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(304) Example B62 includes the subject matter of any of Examples B31-61, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic

component are conductively coupled to conductive contacts at the first face of the bridge component.

(305) Example B63 includes the subject matter of any of Examples B31-62, and further specifies that the microelectronic component includes a die.

(306) Example B64 includes the subject matter of any of Examples B31-63, and further includes: a fill compound between the microelectronic component and the substrate.

(307) Example B65 includes the subject matter of Example B64, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(308) Example B66 includes the subject matter of any of Examples B31-65, and further specifies that the microelectronic component includes a transistor.

(309) Example B67 includes the subject matter of any of Examples B31-66, and further specifies that the microelectronic component includes a memory device.

(310) Example B68 includes the subject matter of any of Examples B31-67, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(311) Example B69 includes the subject matter of any of Examples B31-68, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(312) Example B70 includes the subject matter of Example B69, and further specifies that the surface finish further includes palladium and gold.

(313) Example B71 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity in a face of the substrate, wherein the substrate includes a buildup material, and the cavity extends into the buildup material; a metal at a bottom of the cavity; a bridge component in the cavity; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the substrate, and some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the bridge component.

(314) Example B72 includes the subject matter of Example B71, and further specifies that the substrate includes an organic dielectric material.

(315) Example B73 includes the subject matter of any of Examples B71-72, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(316) Example B74 includes the subject matter of Example B73, and further includes: solder on the conductive contact of the substrate.

(317) Example B75 includes the subject matter of any of Examples B73-74, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(318) Example B76 includes the subject matter of Example B75, and further specifies that the second conductive contact is a second-level interconnect contact.

(319) Example B77 includes the subject matter of any of Examples B71-76, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(320) Example B78 includes the subject matter of any of Examples B71-77, and further specifies that a metal at a bottom of the cavity is adjacent to a metal line of an interior metal layer of the substrate.

- (321) Example B79 includes the subject matter of Example B78, and further specifies that the metal line includes copper.
- (322) Example B80 includes the subject matter of Example B79, and further specifies that the metal is different from copper.
- (323) Example B81 includes the subject matter of any of Examples B78-80, and further specifies that the metal has a thickness that is less than a thickness of the metal line.
- (324) Example B82 includes the subject matter of any of Examples B71-81, and further specifies that the metal extends onto side faces of the cavity.
- (325) Example B83 includes the subject matter of any of Examples B71-81, and further specifies that the metal does not extend onto side faces of the cavity.
- (326) Example B84 includes the subject matter of any of Examples B71-83, and further specifies that the thickness of the metal is less than 1 micron.
- (327) Example B85 includes the subject matter of any of Examples B71-84, and further specifies that the bridge component is coupled to the metal.
- (328) Example B86 includes the subject matter of any of Examples B71-85, and further includes: an adhesive between the bridge component and the metal.
- (329) Example B87 includes the subject matter of Example B86, and further specifies that the adhesive includes a snap-curable adhesive.
- (330) Example B88 includes the subject matter of any of Examples B86-87, and further specifies that the adhesive includes a UV-curable adhesive.
- (331) Example B89 includes the subject matter of any of Examples B86-87, and further specifies that the adhesive includes a first adhesive region and a second adhesive region, and a material composition of the first adhesive region is different from a material composition of the second adhesive region.
- (332) Example B90 includes the subject matter of Example B89, and further specifies that the first adhesive region is proximate to edges of the bridge component and the second adhesive region is proximate to an interior of the bridge component.
- (333) Example B91 includes the subject matter of any of Examples B89-90, and further specifies that the second adhesive region includes a thermally curable adhesive and the first adhesive region includes a snap-curable adhesive.
- (334) Example B92 includes the subject matter of any of Examples B86-91, and further specifies that the metal does not extend outside the region between the adhesive and the bottom of the cavity.
- (335) Example B93 includes the subject matter of any of Examples B71-92, and further specifies that the metal includes aluminum.
- (336) Example B94 includes the subject matter of any of Examples B71-93, and further specifies that the metal includes gold.
- (337) Example B95 includes the subject matter of any of Examples B71-94, and further specifies that a diameter of an opening of the cavity is greater than a diameter of a bottom of the cavity by greater than 5 microns.
- (338) Example B96 includes the subject matter of any of Examples B71-95, and further specifies that a bottom of the cavity has an undulating surface.
- (339) Example B97 includes the subject matter of Example B96, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.
- (340) Example B98 includes the subject matter of any of Examples B71-97, and further specifies that surface insulation material of the substrate has a thickness between 10 microns and 30 microns.
- (341) Example B99 includes the subject matter of any of Examples B71-98, and further specifies that the bridge component includes a semiconductor material.
- (342) Example B100 includes the subject matter of any of Examples B71-99, and further specifies that the bridge component has a thickness that is less than 100 microns.
- (343) Example B101 includes the subject matter of any of Examples B71-100, and further specifies

that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(344) Example B102 includes the subject matter of any of Examples B71-101, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(345) Example B103 includes the subject matter of any of Examples B71-102, and further specifies that the microelectronic component includes a die.

(346) Example B104 includes the subject matter of any of Examples B71-103, and further includes: a fill compound between the microelectronic component and the substrate.

(347) Example B105 includes the subject matter of Example B104, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(348) Example B106 includes the subject matter of any of Examples B71-105, and further specifies that the microelectronic component includes a transistor.

(349) Example B107 includes the subject matter of any of Examples B71-106, and further specifies that the microelectronic component includes a memory device.

(350) Example B108 includes the subject matter of any of Examples B71-107, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(351) Example B109 includes the subject matter of any of Examples B71-108, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(352) Example B110 includes the subject matter of Example B109, and further specifies that the surface finish further includes palladium and gold.

(353) Example B111 includes the subject matter of any of Examples B71-110, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(354) Example B112 includes the subject matter of any of Examples B71-111, and further specifies that the circuit board is a motherboard.

(355) Example B113 includes the subject matter of any of Examples B71-112, and further includes: a display communicatively coupled to the circuit board.

(356) Example B114 includes the subject matter of any of Examples B113, and further specifies that the display includes a touchscreen display.

(357) Example B115 includes the subject matter of any of Examples B71-114, and further includes: a housing around the circuit board and the microelectronic assembly.

(358) Example B116 is bonding equipment including a bond head and an ultraviolet (UV) light source.

(359) Example B117 includes the subject matter of Example B116, and further specifies that the UV light source is coupled to the bond head.

(360) Example C1 is a microelectronic structure, including: a substrate; a cavity at a face of the substrate; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component; a conductive contact at a face of the substrate; and a material between solder and the conductive contact.

(361) Example C2 includes the subject matter of Example C1, and further specifies that the substrate includes an organic dielectric material.

(362) Example C3 includes the subject matter of any of Examples C1-2, and further specifies that the material includes a metal.

(363) Example C4 includes the subject matter of Example C3, and further specifies that the material includes a metal ball.

(364) Example C5 includes the subject matter of Example C4, and further specifies that the metal ball has a diameter that is between 10 microns and 500 microns.

(365) Example C6 includes the subject matter of Example C3, and further specifies that the material includes a metal pillar.

(366) Example C7 includes the subject matter of Example C6, and further specifies that the metal pillar extends past a top surface of a surface insulation material of the substrate by a distance between 10 microns and 50 microns.

(367) Example C8 includes the subject matter of any of Examples C6-7, and further specifies that the metal pillar includes a surface finish on a bulk metal.

(368) Example C9 includes the subject matter of Example C8, and further specifies that the bulk metal includes copper.

(369) Example C10 includes the subject matter of any of Examples C8-9, and further specifies that the surface finish includes nickel, palladium, or gold.

(370) Example C11 includes the subject matter of any of Examples C8-10, and further specifies that the bulk metal is undercut relative to the surface finish.

(371) Example C12 includes the subject matter of any of Examples C3-11, and further specifies that the metal includes copper.

(372) Example C13 includes the subject matter of any of Examples C3-12, and further specifies that the metal includes nickel, palladium, or gold.

(373) Example C14 includes the subject matter of any of Examples C1-2, and further specifies that the solder is a first solder, the material is a second solder, and the first solder has a different material composition than the second solder.

(374) Example C15 includes the subject matter of Example C14, and further specifies that the second solder has a higher melting point than the first solder.

(375) Example C16 includes the subject matter of any of Examples C14-15, and further includes: a third solder between the second solder and the conductive contact, wherein the third solder has a different material composition than the second solder.

(376) Example C17 includes the subject matter of Example C16, and further specifies that the second solder has a higher melting point than the third solder.

(377) Example C18 includes the subject matter of any of Examples C1-17, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(378) Example C19 includes the subject matter of Example C18, and further specifies that the second conductive contact is a second-level interconnect contact.

(379) Example C20 includes the subject matter of any of Examples C1-19, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(380) Example C21 includes the subject matter of any of Examples C1-20, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(381) Example C22 includes the subject matter of Example C21, and further specifies that the bridge component is coupled to the dielectric material.

(382) Example C23 includes the subject matter of Example C22, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.

(383) Example C24 includes the subject matter of any of Examples C21-23, and further specifies that the bottom of the cavity is coplanar with a bottom of the conductive contact.

(384) Example C25 includes the subject matter of any of Examples C1-24, and further specifies that a bottom of the cavity has an undulating surface.

(385) Example C26 includes the subject matter of Example C25, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(386) Example C27 includes the subject matter of Example C25, and further specifies that the undulations have an amplitude that is less than 1 micron.

(387) Example C28 includes the subject matter of any of Examples C1-27, and further specifies that a surface insulation material proximate to the conductive contact of the substrate has a thickness between 10 microns and 30 microns.

(388) Example C29 includes the subject matter of any of Examples C1-28, and further specifies that the bridge component includes a semiconductor material.

(389) Example C30 includes the subject matter of any of Examples C1-29, and further specifies that the bridge component has a thickness that is less than 100 microns.

(390) Example C31 is a microelectronic assembly, including: a substrate; a cavity at a face of the substrate; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes conductive contacts at the first face of the bridge component; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, a conductive contact of the microelectronic component is conductively coupled, by an interconnect, to a conductive contact of the substrate at the face of the substrate, and a conductive contact of the microelectronic component is conductively coupled to a conductive contact at the first face of the bridge component; wherein the interconnect includes solder and a material between the solder and the conductive contact of the substrate, and the material extends beyond a surface of a surface insulation material proximate to the conductive contact of the substrate.

(391) Example C32 includes the subject matter of Example C31, and further specifies that the substrate includes an organic dielectric material.

(392) Example C33 includes the subject matter of any of Examples C31-32, and further specifies that the material includes a metal.

(393) Example C34 includes the subject matter of Example C33, and further specifies that the material includes a metal ball.

(394) Example C35 includes the subject matter of Example C34, and further specifies that the metal ball has a diameter that is between 10 microns and 500 microns.

(395) Example C36 includes the subject matter of Example C33, and further specifies that the material includes a metal pillar.

(396) Example C37 includes the subject matter of Example C36, and further specifies that the metal pillar extends past a top surface of the surface insulation material by a distance between 10 microns and 50 microns.

(397) Example C38 includes the subject matter of any of Examples C36-37, and further specifies that the metal pillar includes a surface finish on a bulk metal.

(398) Example C39 includes the subject matter of Example C38, and further specifies that the bulk metal includes copper.

(399) Example C40 includes the subject matter of any of Examples C38-39, and further specifies that the surface finish includes nickel, palladium, or gold.

(400) Example C41 includes the subject matter of any of Examples C38-40, and further specifies that the bulk metal is undercut relative to the surface finish.

(401) Example C42 includes the subject matter of any of Examples C33-41, and further specifies that the metal includes copper.

(402) Example C43 includes the subject matter of any of Examples C33-42, and further specifies that the metal includes nickel, palladium, or gold.

(403) Example C44 includes the subject matter of any of Examples C31-32, and further specifies that the solder is a first solder, the material is a second solder, and the first solder has a different material composition than the second solder.

(404) Example C45 includes the subject matter of Example C44, and further specifies that the second solder has a higher melting point than the first solder.

(405) Example C46 includes the subject matter of any of Examples C44-45, and further includes: a third solder between the second solder and the conductive contact, wherein the third solder has a different material composition than the second solder.

(406) Example C47 includes the subject matter of Example C46, and further specifies that the second solder has a higher melting point than the third solder.

(407) Example C48 includes the subject matter of any of Examples C31-47, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(408) Example C49 includes the subject matter of Example C48, and further specifies that the second conductive contact is a second-level interconnect contact.

(409) Example C50 includes the subject matter of any of Examples C31-49, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(410) Example C51 includes the subject matter of any of Examples C31-50, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(411) Example C52 includes the subject matter of Example C51, and further specifies that the bridge component is coupled to the dielectric material.

(412) Example C53 includes the subject matter of Example C52, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.

(413) Example C54 includes the subject matter of any of Examples C51-53, and further specifies that the bottom of the cavity is coplanar with a bottom of the conductive contact.

(414) Example C55 includes the subject matter of any of Examples C31-54, and further specifies that a bottom of the cavity has an undulating surface.

(415) Example C56 includes the subject matter of Example C55, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(416) Example C57 includes the subject matter of Example C55, and further specifies that the undulations have an amplitude that is less than 1 micron.

(417) Example C58 includes the subject matter of any of Examples C31-57, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(418) Example C59 includes the subject matter of any of Examples C31-58, and further specifies that the bridge component includes a semiconductor material.

(419) Example C60 includes the subject matter of any of Examples C31-59, and further specifies that the bridge component has a thickness that is less than 100 microns.

(420) Example C61 includes the subject matter of any of Examples C31-60, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(421) Example C62 includes the subject matter of any of Examples C31-61, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing

second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(422) Example C63 includes the subject matter of any of Examples C31-62, and further specifies that the microelectronic component includes a die.

(423) Example C64 includes the subject matter of any of Examples C31-63, and further includes: a fill compound between the microelectronic component and the substrate.

(424) Example C65 includes the subject matter of Example C64, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(425) Example C66 includes the subject matter of any of Examples C31-65, and further specifies that the microelectronic component includes a transistor.

(426) Example C67 includes the subject matter of any of Examples C31-66, and further specifies that the microelectronic component includes a memory device.

(427) Example C68 includes the subject matter of any of Examples C31-67, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(428) Example C69 includes the subject matter of any of Examples C31-68, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(429) Example C70 includes the subject matter of Example C69, and further specifies that the surface finish further includes palladium and gold.

(430) Example C71 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity at a face of the substrate; a bridge component in the cavity; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, a conductive contact of the microelectronic component is coupled, by an interconnect, to a conductive contact of the substrate, and a conductive contact of the microelectronic component is coupled to a conductive contact of the bridge component; wherein the conductive contact of the substrate is at a bottom of an opening in a surface insulation material, the interconnect includes solder and a material, and the material fills a majority of a volume of the opening.

(431) Example C72 includes the subject matter of Example C71, and further specifies that the substrate includes an organic dielectric material.

(432) Example C73 includes the subject matter of any of Examples C71-72, and further specifies that the material includes a metal.

(433) Example C74 includes the subject matter of Example C73, and further specifies that the material includes a metal ball.

(434) Example C75 includes the subject matter of Example C74, and further specifies that the metal ball has a diameter that is between 10 microns and 500 microns.

(435) Example C76 includes the subject matter of Example C73, and further specifies that the material includes a metal pillar.

(436) Example C77 includes the subject matter of Example C76, and further specifies that the metal pillar extends past a top surface of the surface insulation material by a distance between 10 microns and 50 microns.

(437) Example C78 includes the subject matter of any of Examples C76-77, and further specifies

that the metal pillar includes a surface finish on a bulk metal.

(438) Example C79 includes the subject matter of Example C78, and further specifies that the bulk metal includes copper.

(439) Example C80 includes the subject matter of any of Examples C78-79, and further specifies that the surface finish includes nickel, palladium, or gold.

(440) Example C81 includes the subject matter of any of Examples C78-80, and further specifies that the bulk metal is undercut relative to the surface finish.

(441) Example C82 includes the subject matter of any of Examples C73-81, and further specifies that the metal includes copper.

(442) Example C83 includes the subject matter of any of Examples C73-82, and further specifies that the metal includes nickel, palladium, or gold.

(443) Example C84 includes the subject matter of any of Examples C71-72, and further specifies that the solder is a first solder, the material is a second solder, and the first solder has a different material composition than the second solder.

(444) Example C85 includes the subject matter of Example C84, and further specifies that the second solder has a higher melting point than the first solder.

(445) Example C86 includes the subject matter of any of Examples C84-85, and further includes: a third solder between the second solder and the conductive contact of the substrate, wherein the third solder has a different material composition than the second solder.

(446) Example C87 includes the subject matter of Example C86, and further specifies that the second solder has a higher melting point than the third solder.

(447) Example C88 includes the subject matter of any of Examples C71-87, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(448) Example C89 includes the subject matter of any of Examples C88, and further specifies that the second conductive contact is a second-level interconnect contact.

(449) Example C90 includes the subject matter of any of Examples C71-89, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(450) Example C91 includes the subject matter of any of Examples C71-90, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(451) Example C92 includes the subject matter of Example C91, and further specifies that the bridge component is coupled to the dielectric material.

(452) Example C93 includes the subject matter of Example C92, and further specifies that the bridge component is coupled to the dielectric material by an adhesive.

(453) Example C94 includes the subject matter of any of Examples C91-93, and further specifies that the bottom of the cavity is coplanar with a bottom of the conductive contact.

(454) Example C95 includes the subject matter of any of Examples C71-94, and further specifies that a bottom of the cavity has an undulating surface.

(455) Example C96 includes the subject matter of Example C95, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(456) Example C97 includes the subject matter of Example C95, and further specifies that the undulations have an amplitude that is less than 1 micron.

(457) Example C98 includes the subject matter of any of Examples C71-97, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(458) Example C99 includes the subject matter of any of Examples C71-98, and further specifies that the bridge component includes a semiconductor material.

(459) Example C100 includes the subject matter of any of Examples C71-99, and further specifies

that the bridge component has a thickness that is less than 100 microns.

(460) Example C101 includes the subject matter of any of Examples C71-100, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(461) Example C102 includes the subject matter of any of Examples C71-101, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(462) Example C103 includes the subject matter of any of Examples C71-102, and further specifies that the microelectronic component includes a die.

(463) Example C104 includes the subject matter of any of Examples C71-103, and further includes: a fill compound between the microelectronic component and the substrate.

(464) Example C105 includes the subject matter of Example C104, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(465) Example C106 includes the subject matter of any of Examples C71-105, and further specifies that the microelectronic component includes a transistor.

(466) Example C107 includes the subject matter of any of Examples C71-106, and further specifies that the microelectronic component includes a memory device.

(467) Example C108 includes the subject matter of any of Examples C71-107, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(468) Example C109 includes the subject matter of any of Examples C71-108, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(469) Example C110 includes the subject matter of Example C109, and further specifies that the surface finish further includes palladium and gold.

(470) Example C111 includes the subject matter of any of Examples C71-110, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(471) Example C112 includes the subject matter of any of Examples C71-111, and further specifies that the circuit board is a motherboard.

(472) Example C113 includes the subject matter of any of Examples C71-112, and further includes: a display communicatively coupled to the circuit board.

(473) Example C114 includes the subject matter of Example C113, and further specifies that the display includes a touchscreen display.

(474) Example C115 includes the subject matter of any of Examples C71-114, and further includes: a housing around the circuit board and the microelectronic assembly.

(475) Example D1 is a microelectronic structure, including: a substrate; a cavity at a face of the substrate; a first conductive contact of the substrate at a bottom of the cavity; a second conductive contact of the substrate outside the cavity; first solder on the first conductive contact; and second solder on the second conductive contact, wherein the first solder and the second solder have different material compositions.

(476) Example D2 includes the subject matter of Example D1, and further specifies that the first solder and the second solder have different melting temperatures.

(477) Example D3 includes the subject matter of any of Examples D1-2, and further specifies that

the first solder has a higher melting point than the second solder.

(478) Example D4 includes the subject matter of any of Examples D1-3, and further includes: a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, the bridge component includes a first conductive contact at the first face of the bridge component, the bridge component includes a second conductive contact at the second face of the bridge component, and the second conductive contact of the bridge component is coupled to the first conductive contact of the substrate by the first solder.

(479) Example D5 includes the subject matter of any of Examples D1-4, and further specifies that the substrate includes an organic dielectric material.

(480) Example D6 includes the subject matter of any of Examples D1-2, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the second conductive contact of the substrate is at a bottom of the opening.

(481) Example D7 includes the subject matter of any of Examples D3-4, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(482) Example D8 includes the subject matter of Example D7, and further specifies that the third conductive contact is a second-level interconnect contact.

(483) Example D9 includes the subject matter of any of Examples D1-8, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(484) Example D10 includes the subject matter of any of Examples D1-9, and further specifies that a dielectric material of the substrate is at a bottom of the cavity.

(485) Example D11 includes the subject matter of any of Examples D1-10, and further specifies that the bridge component includes a semiconductor material.

(486) Example D12 includes the subject matter of any of Examples D1-11, and further specifies that the bridge component has a thickness that is less than 100 microns.

(487) Example D13 is a microelectronic assembly, including: a substrate; a cavity at a face of the substrate; a first conductive contact of the substrate outside the cavity; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes a second conductive contact at the first face of the bridge component; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, a first conductive contact of the microelectronic component is conductively coupled to the first conductive contact of the substrate, and a second conductive contact of the microelectronic component is conductively coupled, by an interconnect, to the second conductive contact of the bridge component; wherein the interconnect includes a first solder material and a second solder material different from the first solder material.

(488) Example D14 includes the subject matter of Example D13, and further specifies that the first solder material is between the second solder material and the second conductive contact of the microelectronic component.

(489) Example D15 includes the subject matter of any of Examples D13-14, and further specifies that the first solder material has a different melting point than the second solder material.

(490) Example D16 includes the subject matter of any of Examples D13-14, and further specifies that the first solder material has a higher melting point than the second solder material.

(491) Example D17 includes the subject matter of any of Examples D13-16, and further specifies that the interconnect is a first interconnect, the first conductive contact of the microelectronic

component is conductively coupled to the first conductive contact of the substrate by a second interconnect, and the second interconnect includes a third solder material and a fourth solder material different from the third solder material.

(492) Example D18 includes the subject matter of Example D17, and further specifies that the third solder material is between the fourth solder material and the first conductive contact of the microelectronic component.

(493) Example D19 includes the subject matter of any of Examples D17-18, and further specifies that the third solder material has a different melting point than the fourth solder material.

(494) Example D20 includes the subject matter of any of Examples D17-19, and further specifies that the third solder material has a higher melting point than the fourth solder material.

(495) Example D21 includes the subject matter of any of Examples D17-20, and further specifies that the second interconnect further includes a fifth solder material different from the fourth solder material.

(496) Example D22 includes the subject matter of Example D21, and further specifies that the fourth solder material is between the fifth solder material and the third solder material.

(497) Example D23 includes the subject matter of any of Examples D21-22, and further specifies that the fourth solder material has a different melting point than the fifth solder material.

(498) Example D24 includes the subject matter of any of Examples D21-23, and further specifies that the fourth solder material has a lower melting point than the fifth solder material.

(499) Example D25 includes the subject matter of any of Examples D21-24, and further specifies that the fifth solder material has a same material composition as the third solder material.

(500) Example D26 includes the subject matter of any of Examples D21-25, and further specifies that the fifth solder material has a same material composition as the first solder material.

(501) Example D27 includes the subject matter of any of Examples D17-26, and further specifies that the fourth solder material has a same material composition as the second solder material.

(502) Example D28 includes the subject matter of any of Examples D17-27, and further specifies that the third solder material has a same material composition as the first solder material.

(503) Example D29 includes the subject matter of any of Examples D13-16, and further specifies that the interconnect is a first interconnect, the first conductive contact of the microelectronic component is conductively coupled to the first conductive contact of the substrate by a second interconnect, and the second interconnect includes a third solder material.

(504) Example D30 includes the subject matter of Example D29, and further specifies that the third solder material has a same material composition as the first solder material.

(505) Example D31 includes the subject matter of any of Examples D13-30, and further specifies that the substrate further includes a second conductive contact in the cavity, the bridge component includes a third conductive contact at the second face of the bridge component, and the second conductive contact of the substrate is coupled to the third conductive contact of the bridge component by solder.

(506) Example D32 includes the subject matter of Example D31, and further specifies that the solder has a same material composition as the first solder.

(507) Example D33 includes the subject matter of any of Examples D13-32, and further specifies that the substrate includes an organic dielectric material.

(508) Example D34 includes the subject matter of any of Examples D13-32, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the first conductive contact of the substrate is at a bottom of the opening.

(509) Example D35 includes the subject matter of any of Examples D13-34, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(510) Example D36 includes the subject matter of Example D35, and further specifies that the third conductive contact is a second-level interconnect contact.

(511) Example D37 includes the subject matter of any of Examples D13-36, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(512) Example D38 includes the subject matter of any of Examples D13-37, and further specifies that a bottom of the cavity has an undulating surface.

(513) Example D39 includes the subject matter of Example D38, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(514) Example D40 includes the subject matter of Example D38, and further specifies that the undulations have an amplitude that is less than 1 micron.

(515) Example D41 includes the subject matter of any of Examples D13-40, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(516) Example D42 includes the subject matter of any of Examples D13-41, and further specifies that the bridge component includes a semiconductor material.

(517) Example D43 includes the subject matter of any of Examples D13-42, and further specifies that the bridge component has a thickness that is less than 100 microns.

(518) Example D44 includes the subject matter of any of Examples D13-43, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(519) Example D45 includes the subject matter of any of Examples D13-44, and further specifies that the first conductive contact of the microelectronic component has a different area than the second conductive contact of the microelectronic component.

(520) Example D46 includes the subject matter of any of Examples D13-45, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(521) Example D47 includes the subject matter of any of Examples D13-46, and further specifies that the microelectronic component includes a die.

(522) Example D48 includes the subject matter of any of Examples D13-47, and further includes: a fill compound between the microelectronic component and the substrate.

(523) Example D49 includes the subject matter of Example D48, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(524) Example D50 includes the subject matter of any of Examples D13-49, and further specifies that the microelectronic component includes a transistor.

(525) Example D51 includes the subject matter of any of Examples D13-50, and further specifies that the microelectronic component includes a memory device.

(526) Example D52 includes the subject matter of any of Examples D13-51, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(527) Example D53 includes the subject matter of any of Examples D13-52, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(528) Example D54 includes the subject matter of Example D53, and further specifies that the surface finish further includes palladium and gold.

(529) Example D55 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity at a face of the substrate; a bridge component in the cavity; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, a first conductive contact of the microelectronic component is conductively coupled to the first conductive contact of the substrate, and a second conductive contact of the microelectronic component is conductively coupled, by an interconnect, to the second conductive contact of the bridge component; wherein the interconnect includes a first solder material and a second solder material different from the first solder material.

(530) Example D56 includes the subject matter of Example D55, and further specifies that the first solder material is between the second solder material and the second conductive contact of the microelectronic component.

(531) Example D57 includes the subject matter of any of Examples D55-56, and further specifies that the first solder material has a different melting point than the second solder material.

(532) Example D58 includes the subject matter of any of Examples D55-56, and further specifies that the first solder material has a higher melting point than the second solder material.

(533) Example D59 includes the subject matter of any of Examples D55-58, and further specifies that the interconnect is a first interconnect, the first conductive contact of the microelectronic component is conductively coupled to the first conductive contact of the substrate by a second interconnect, and the second interconnect includes a third solder material and a fourth solder material different from the third solder material.

(534) Example D60 includes the subject matter of Example D59, and further specifies that the third solder material is between the fourth solder material and the first conductive contact of the microelectronic component.

(535) Example D61 includes the subject matter of any of Examples D59-60, and further specifies that the third solder material has a different melting point than the fourth solder material.

(536) Example D62 includes the subject matter of any of Examples D59-61, and further specifies that the third solder material has a higher melting point than the fourth solder material.

(537) Example D63 includes the subject matter of any of Examples D59-62, and further specifies that the second interconnect further includes a fifth solder material different from the fourth solder material.

(538) Example D64 includes the subject matter of Example D63, and further specifies that the fourth solder material is between the fifth solder material and the third solder material.

(539) Example D65 includes the subject matter of any of Examples D63-64, and further specifies that the fourth solder material has a different melting point than the fifth solder material.

(540) Example D66 includes the subject matter of any of Examples D63-65, and further specifies that the fourth solder material has a lower melting point than the fifth solder material.

(541) Example D67 includes the subject matter of any of Examples D63-66, and further specifies that the fifth solder material has a same material composition as the third solder material.

(542) Example D68 includes the subject matter of any of Examples D63-67, and further specifies that the fifth solder material has a same material composition as the first solder material.

(543) Example D69 includes the subject matter of any of Examples D59-68, and further specifies that the fourth solder material has a same material composition as the second solder material.

(544) Example D70 includes the subject matter of any of Examples D59-69, and further specifies that the third solder material has a same material composition as the first solder material.

(545) Example D71 includes the subject matter of any of Examples D55-58, and further specifies that the interconnect is a first interconnect, the first conductive contact of the microelectronic component is conductively coupled to the first conductive contact of the substrate by a second

interconnect, and the second interconnect includes a third solder material.

(546) Example D72 includes the subject matter of Example D71, and further specifies that the third solder material has a same material composition as the first solder material.

(547) Example D73 includes the subject matter of any of Examples D55-72, and further specifies that the substrate further includes a second conductive contact in the cavity, the bridge component includes a third conductive contact at the second face of the bridge component, and the second conductive contact of the substrate is coupled to the third conductive contact of the bridge component by solder.

(548) Example D74 includes the subject matter of any of Examples D73, and further specifies that the solder has a same material composition as the first solder.

(549) Example D75 includes the subject matter of any of Examples D55-74, and further specifies that the substrate includes an organic dielectric material.

(550) Example D76 includes the subject matter of any of Examples D55-75, and further specifies that the substrate includes a surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(551) Example D77 includes the subject matter of any of Examples D55-76, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(552) Example D78 includes the subject matter of Example D77, and further specifies that the third conductive contact is a second-level interconnect contact.

(553) Example D79 includes the subject matter of any of Examples D55-78, and further specifies that the first conductive contact of the microelectronic component has a different area than the second conductive contact of the microelectronic component.

(554) Example D80 includes the subject matter of any of Examples D55-79, and further specifies that the first conductive contact of the microelectronic component has a larger area than the second conductive contact of the microelectronic component.

(555) Example D81 includes the subject matter of any of Examples D55-80, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(556) Example D82 includes the subject matter of any of Examples D55-81, and further specifies that a bottom of the cavity has an undulating surface.

(557) Example D83 includes the subject matter of Example D82, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(558) Example D84 includes the subject matter of Example D82, and further specifies that the undulations have an amplitude that is less than 1 micron.

(559) Example D85 includes the subject matter of any of Examples D55-84, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(560) Example D86 includes the subject matter of any of Examples D55-85, and further specifies that the bridge component includes a semiconductor material.

(561) Example D87 includes the subject matter of any of Examples D55-86, and further specifies that the bridge component has a thickness that is less than 100 microns.

(562) Example D88 includes the subject matter of any of Examples D55-87, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(563) Example D89 includes the subject matter of any of Examples D55-88, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the

second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(564) Example D90 includes the subject matter of any of Examples D55-89, and further specifies that the microelectronic component includes a die.

(565) Example D91 includes the subject matter of any of Examples D55-90, and further includes: a fill compound between the microelectronic component and the substrate.

(566) Example D92 includes the subject matter of Example D91, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(567) Example D93 includes the subject matter of any of Examples D55-92, and further specifies that the microelectronic component includes a transistor.

(568) Example D94 includes the subject matter of any of Examples D55-93, and further specifies that the microelectronic component includes a memory device.

(569) Example D95 includes the subject matter of any of Examples D55-94, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(570) Example D96 includes the subject matter of any of Examples D55-95, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(571) Example D97 includes the subject matter of Example D96, and further specifies that the surface finish further includes palladium and gold.

(572) Example D98 includes the subject matter of any of Examples D55-97, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(573) Example D99 includes the subject matter of any of Examples D55-98, and further specifies that the circuit board is a motherboard.

(574) Example D100 includes the subject matter of any of Examples D55-99, and further includes: a display communicatively coupled to the circuit board.

(575) Example D101 includes the subject matter of Example D100, and further specifies that the display includes a touchscreen display.

(576) Example D102 includes the subject matter of any of Examples D55-101, and further includes: a housing around the circuit board and the microelectronic assembly.

(577) Example E1 is a microelectronic structure, including: a substrate; a cavity at a face of the substrate; a first conductive contact in the cavity; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes a second conductive contact at the second face of the bridge component; wherein the first conductive contact is electrically coupled to the second conductive contact, and the first conductive contact in the cavity has a non-planar contact surface.

(578) Example E2 includes the subject matter of Example E1, and further specifies that the substrate includes an organic dielectric material.

(579) Example E3 includes the subject matter of any of Examples E1-2, and further specifies that the substrate includes a third conductive contact outside the cavity at the face of the substrate, the substrate includes surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the third conductive contact of the substrate is at a bottom of the opening.

(580) Example E4 includes the subject matter of Example E3, and further includes: solder on the third conductive contact of the substrate.

(581) Example E5 includes the subject matter of any of Examples E3-4, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(582) Example E6 includes the subject matter of Example E5, and further specifies that the third conductive contact is a second-level interconnect contact.

(583) Example E7 includes the subject matter of any of Examples E1-6, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(584) Example E8 includes the subject matter of any of Examples E1-7, and further specifies that the first conductive contact includes a wire.

(585) Example E9 includes the subject matter of Example E8, and further specifies that the wire includes copper, silver, or gold.

(586) Example E10 includes the subject matter of any of Examples E1-9, and further specifies that the contact surface includes a pointed shape.

(587) Example E11 includes the subject matter of any of Examples E1-9, and further specifies that the contact surface has an arc shape.

(588) Example E12 includes the subject matter of any of Examples E11, and further specifies that the first conductive contact includes a dome of multiple wires.

(589) Example E13 includes the subject matter of any of Examples E1-9, and further specifies that the first conductive contact includes a cantilever.

(590) Example E14 includes the subject matter of any of Examples E1-13, and further specifies that the first conductive contact includes a wire that is wirebonded to metal of a metal layer of the substrate.

(591) Example E15 includes the subject matter of any of Examples E1-14, and further specifies that the substrate includes a surface insulation material at the face of the substrate, and the cavity extends at least through the surface insulation material.

(592) Example E16 includes the subject matter of Example E15, and further specifies that the cavity extends past the surface insulation material into a dielectric material of the substrate.

(593) Example E17 includes the subject matter of any of Examples E15-16, and further specifies that the first conductive contact does not extend past a plane of a lower surface of the surface insulation material.

(594) Example E18 includes the subject matter of any of Examples E1-17, and further specifies that the first conductive contact is electrically coupled to the second conductive contact by solder.

(595) Example E19 includes the subject matter of any of Examples E1-18, and further specifies that the first conductive contact is one of a plurality of first conductive contacts in a cavity of the substrate, and the plurality of first conductive contacts have non-planar contact surfaces.

(596) Example E20 includes the subject matter of any of Examples E1-19, and further includes: an underfill material between the second face of the bridge component and the substrate.

(597) Example E21 includes the subject matter of Example E20, and further specifies that the first conductive contact includes a wire, and the underfill material is around the wire.

(598) Example E22 includes the subject matter of any of Examples E1-21, and further specifies that the bridge component includes a conductive pathway between the second conductive contact of the bridge component and a conductive contact on the first face of the bridge component.

(599) Example E23 includes the subject matter of any of Examples E1-22, and further specifies that the bridge component does not contact a dielectric material of the substrate.

(600) Example E24 includes the subject matter of any of Examples E1-23, and further specifies that the bridge component includes a transistor.

(601) Example E25 includes the subject matter of any of Examples E1-24, and further specifies that a bottom of the cavity has an undulating surface.

(602) Example E26 includes the subject matter of Example E25, and further specifies that the

undulations have an amplitude between 1 micron and 10 microns.

(603) Example E27 includes the subject matter of Example E25, and further specifies that the undulations have an amplitude that is less than 1 micron.

(604) Example E28 includes the subject matter of any of Examples E1-27, and further specifies that the surface insulation material has a thickness between 10 microns and 30 microns.

(605) Example E29 includes the subject matter of any of Examples E1-28, and further specifies that the bridge component includes a semiconductor material.

(606) Example E30 includes the subject matter of any of Examples E1-29, and further specifies that the bridge component has a thickness that is less than 100 microns.

(607) Example E31 is a microelectronic assembly, including: a substrate; a cavity at a face of the substrate; a first conductive contact in the cavity, wherein the first conductive contact has a non-planar contact surface; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, and the bridge component includes a second conductive contact at the first face of the bridge component; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(608) Example E32 includes the subject matter of Example E31, and further specifies that the substrate includes an organic dielectric material.

(609) Example E33 includes the subject matter of any of Examples E31-32, and further specifies that the substrate includes a third conductive contact outside the cavity at the face of the substrate, the substrate includes surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the third conductive contact of the substrate is at a bottom of the opening.

(610) Example E34 includes the subject matter of Example E33, and further includes: solder on the third conductive contact of the substrate.

(611) Example E35 includes the subject matter of any of Examples E33-34, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(612) Example E36 includes the subject matter of Example E35, and further specifies that the third conductive contact is a second-level interconnect contact.

(613) Example E37 includes the subject matter of any of Examples E31-36, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(614) Example E38 includes the subject matter of any of Examples E31-37, and further specifies that the first conductive contact includes a wire.

(615) Example E39 includes the subject matter of Example E38, and further specifies that the wire includes copper, silver, or gold.

(616) Example E40 includes the subject matter of any of Examples E31-39, and further specifies that the first conductive contact has a point that extends towards the second conductive contact.

(617) Example E41 includes the subject matter of any of Examples E31-39, and further specifies that the first conductive contact has an arc that extends towards the second conductive contact.

(618) Example E42 includes the subject matter of Example E41, and further specifies that the first conductive contact includes a dome of multiple wires.

(619) Example E43 includes the subject matter of any of Examples E31-39, and further specifies

that the first conductive contact includes a cantilever.

(620) Example E44 includes the subject matter of any of Examples E31-43, and further specifies that the first conductive contact includes a wire that is wirebonded to metal of a metal layer of the substrate.

(621) Example E45 includes the subject matter of any of Examples E31-44, and further specifies that the substrate includes a surface insulation material at the face of the substrate, and the cavity extends at least through the surface insulation material.

(622) Example E46 includes the subject matter of Example E45, and further specifies that the cavity extends past the surface insulation material into a dielectric material of the substrate.

(623) Example E47 includes the subject matter of any of Examples E45-46, and further specifies that the first conductive contact does not extend past a plane of a lower surface of the surface insulation material.

(624) Example E48 includes the subject matter of any of Examples E31-47, and further specifies that the first conductive contact is electrically coupled to the second conductive contact by solder.

(625) Example E49 includes the subject matter of any of Examples E31-48, and further specifies that the first conductive contact is one of a plurality of first conductive contacts in a cavity of the substrate, and the plurality of first conductive contacts have non-planar contact surfaces.

(626) Example E50 includes the subject matter of any of Examples E31-49, and further includes: an underfill material between the second face of the bridge component and the substrate.

(627) Example E51 includes the subject matter of Example E50, and further specifies that the first conductive contact includes a wire, and the underfill material is around the wire.

(628) Example E52 includes the subject matter of any of Examples E31-51, and further specifies that the bridge component includes a conductive pathway between the second conductive contact of the bridge component and a conductive contact on the first face of the bridge component.

(629) Example E53 includes the subject matter of any of Examples E31-52, and further specifies that the bridge component does not contact a dielectric material of the substrate.

(630) Example E54 includes the subject matter of any of Examples E31-53, and further specifies that the bridge component includes a transistor.

(631) Example E55 includes the subject matter of any of Examples E31-54, and further specifies that a bottom of the cavity has an undulating surface.

(632) Example E56 includes the subject matter of Example E55, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(633) Example E57 includes the subject matter of Example E55, and further specifies that the undulations have an amplitude that is less than 1 micron.

(634) Example E58 includes the subject matter of any of Examples E31-57, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(635) Example E59 includes the subject matter of any of Examples E31-58, and further specifies that the bridge component includes a semiconductor material.

(636) Example E60 includes the subject matter of any of Examples E31-59, and further specifies that the bridge component has a thickness that is less than 100 microns.

(637) Example E61 includes the subject matter of any of Examples E31-60, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(638) Example E62 includes the subject matter of any of Examples E31-61, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive

contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(639) Example E63 includes the subject matter of any of Examples E31-62, and further specifies that the microelectronic component includes a die.

(640) Example E64 includes the subject matter of any of Examples E31-63, and further includes: a fill compound between the microelectronic component and the substrate.

(641) Example E65 includes the subject matter of Example E64, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(642) Example E66 includes the subject matter of any of Examples E31-65, and further specifies that the microelectronic component includes a transistor.

(643) Example E67 includes the subject matter of any of Examples E31-66, and further specifies that the microelectronic component includes a memory device.

(644) Example E68 includes the subject matter of any of Examples E31-67, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(645) Example E69 includes the subject matter of any of Examples E31-68, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(646) Example E70 includes the subject matter of Example E69, and further specifies that the surface finish further includes palladium and gold.

(647) Example E71 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity at a face of the substrate; a first conductive contact in the cavity; a bridge component in the cavity, wherein the bridge component includes a second conductive contact that faces and is coupled to the first conductive contact, the first conductive contact has a surface, the surface faces the bridge component, and the surface is not flat; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the substrate, and some of the conductive contacts of the microelectronic component are coupled by solder to conductive contacts of the bridge component.

(648) Example E72 includes the subject matter of Example E71, and further specifies that the substrate includes an organic dielectric material.

(649) Example E73 includes the subject matter of any of Examples E71-72, and further specifies that the substrate includes a third conductive contact outside the cavity at the face of the substrate, the substrate includes surface insulation material at the face of the substrate, the surface insulation material includes an opening, and the third conductive contact of the substrate is at a bottom of the opening.

(650) Example E74 includes the subject matter of Example E73, and further includes: solder on the third conductive contact of the substrate.

(651) Example E75 includes the subject matter of any of Examples E73-74, and further specifies that the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a third conductive contact at the second face of the substrate.

(652) Example E76 includes the subject matter of Example E75, and further specifies that the third conductive contact is a second-level interconnect contact.

(653) Example E77 includes the subject matter of any of Examples E71-76, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(654) Example E78 includes the subject matter of any of Examples E71-77, and further specifies that the first conductive contact includes a wire.

(655) Example E79 includes the subject matter of Example E78, and further specifies that the wire includes copper, silver, or gold.

(656) Example E80 includes the subject matter of any of Examples E71-79, and further specifies that the surface includes a pointed shape.

(657) Example E81 includes the subject matter of any of Examples E71-79, and further specifies that the surface includes an arc shape.

(658) Example E82 includes the subject matter of Example E81, and further specifies that the first conductive contact includes a dome of multiple wires.

(659) Example E83 includes the subject matter of any of Examples E71-79, and further specifies that the first conductive contact includes a cantilever.

(660) Example E84 includes the subject matter of any of Examples E71-83, and further specifies that the first conductive contact includes a wire that is wirebonded to metal of a metal layer of the substrate.

(661) Example E85 includes the subject matter of any of Examples E71-84, and further specifies that the substrate includes a surface insulation material at the face of the substrate, and the cavity extends at least through the surface insulation material.

(662) Example E86 includes the subject matter of Example E85, and further specifies that the cavity extends past the surface insulation material into a dielectric material of the substrate.

(663) Example E87 includes the subject matter of any of Examples E85-86, and further specifies that the first conductive contact does not extend past a plane of a lower surface of the surface insulation material.

(664) Example E88 includes the subject matter of any of Examples E71-87, and further specifies that the first conductive contact is electrically coupled to the second conductive contact by solder.

(665) Example E89 includes the subject matter of any of Examples E71-88, and further specifies that the first conductive contact is one of a plurality of first conductive contacts in a cavity of the substrate, and the plurality of first conductive contacts have non-planar contact surfaces.

(666) Example E90 includes the subject matter of any of Examples E71-89, and further includes: an underfill material between the second face of the bridge component and the substrate.

(667) Example E91 includes the subject matter of Example E90, and further specifies that the first conductive contact includes a wire, and the underfill material is around the wire.

(668) Example E92 includes the subject matter of any of Examples E71-91, and further specifies that the bridge component includes a conductive pathway between the second conductive contact of the bridge component and a conductive contact on the first face of the bridge component.

(669) Example E93 includes the subject matter of any of Examples E71-92, and further specifies that the bridge component does not contact a dielectric material of the substrate.

(670) Example E94 includes the subject matter of any of Examples E71-93, and further specifies that the bridge component includes a transistor.

(671) Example E95 includes the subject matter of any of Examples E71-94, and further specifies that a bottom of the cavity has an undulating surface.

(672) Example E96 includes the subject matter of Example E95, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(673) Example E97 includes the subject matter of Example E95, and further specifies that the undulations have an amplitude that is less than 1 micron.

(674) Example E98 includes the subject matter of any of Examples E71-97, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(675) Example E99 includes the subject matter of any of Examples E71-98, and further specifies that the bridge component includes a semiconductor material.

(676) Example E100 includes the subject matter of any of Examples E71-99, and further specifies that the bridge component has a thickness that is less than 100 microns.

(677) Example E101 includes the subject matter of any of Examples E71-100, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(678) Example E102 includes the subject matter of any of Examples E71-101, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(679) Example E103 includes the subject matter of any of Examples E71-102, and further specifies that the microelectronic component includes a die.

(680) Example E104 includes the subject matter of any of Examples E71-103, and further includes: a fill compound between the microelectronic component and the substrate.

(681) Example E105 includes the subject matter of Example E104, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(682) Example E106 includes the subject matter of any of Examples E71-105, and further specifies that the microelectronic component includes a transistor.

(683) Example E107 includes the subject matter of any of Examples E71-106, and further specifies that the microelectronic component includes a memory device.

(684) Example E108 includes the subject matter of any of Examples E71-107, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(685) Example E109 includes the subject matter of any of Examples E71-108, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(686) Example E110 includes the subject matter of Example E109, and further specifies that the surface finish further includes palladium and gold.

(687) Example E111 includes the subject matter of any of Examples E71-110, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(688) Example E112 includes the subject matter of any of Examples E71-111, and further specifies that the circuit board is a motherboard.

(689) Example E113 includes the subject matter of any of Examples E71-112, and further includes: a display communicatively coupled to the circuit board.

(690) Example E114 includes the subject matter of Example E113, and further specifies that the display includes a touchscreen display.

(691) Example E115 includes the subject matter of any of Examples E71-114, and further includes: a housing around the circuit board and the microelectronic assembly.

(692) Example F1 is a microelectronic structure, including: a substrate; a cavity at a face of the substrate; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, the bridge component includes a first interconnect material at the first face of the bridge component, the bridge component includes a second interconnect material at the second face of the bridge component, and the first interconnect material has a different material composition than the second interconnect material.

(693) Example F2 includes the subject matter of Example F1, and further specifies that the first interconnect material includes solder.

(694) Example F3 includes the subject matter of Example F2, and further specifies that the solder of the first interconnect material is a first solder, the second interconnect material includes a second solder, and the second solder has a different material composition than the first solder.

(695) Example F4 includes the subject matter of Example F3, and further specifies that the first solder has a different melting point than the second solder.

(696) Example F5 includes the subject matter of any of Examples F3-4, and further specifies that the first solder has a higher melting point than the second solder.

(697) Example F6 includes the subject matter of any of Examples F3-5, and further specifies that the first solder has a melting point above 200 degrees Celsius, and the second solder has a melting point below 200 degrees Celsius.

(698) Example F7 includes the subject matter of any of Examples F1-6, and further includes: a polymer material around the second interconnect material.

(699) Example F8 includes the subject matter of any of Examples F1-7, and further includes: an epoxy material between the second face of the bridge component and the cavity.

(700) Example F9 includes the subject matter of Example F8, and further specifies that the epoxy material includes an epoxy flux dot.

(701) Example F10 includes the subject matter of Example F8, and further specifies that the epoxy material includes an epoxy flux film.

(702) Example F11 includes the subject matter of any of Examples F1-2, and further specifies that the second interconnect material includes a conductive adhesive, and the conductive adhesive includes a polymer.

(703) Example F12 includes the subject matter of any of Examples F1-2, and further specifies that the second interconnect material includes an intermetallic compound (IMC).

(704) Example F13 includes the subject matter of Example F12, and further specifies that the IMC includes high-temperature solder particles and low-temperature solder particles.

(705) Example F14 includes the subject matter of any of Examples F1-2, and further specifies that the second interconnect material includes a transient liquid phase sintering (TLPS) material.

(706) Example F15 includes the subject matter of any of Examples F1-2 and 14, and further specifies that the second interconnect material includes a polymer, copper, and tin.

(707) Example F16 includes the subject matter of any of Examples F1-15, and further specifies that the substrate includes an organic dielectric material.

(708) Example F17 includes the subject matter of any of Examples F1-16, and further specifies that the substrate includes a conductive contact at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(709) Example F18 includes the subject matter of Example F17, and further includes: solder on the conductive contact of the substrate.

(710) Example F19 includes the subject matter of any of Examples F17-18, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(711) Example F20 includes the subject matter of Example F19, and further specifies that the second conductive contact is a second-level interconnect contact.

(712) Example F21 includes the subject matter of any of Examples F1-20, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(713) Example F22 includes the subject matter of any of Examples F1-21, and further includes: a conductive contact at a bottom of the cavity, wherein the second conductive contact of the bridge

component is coupled to the conductive contact by the second interconnect material.

(714) Example F23 includes the subject matter of Example F22, and further specifies that the conductive contact is part of an N-1 metal layer of the substrate.

(715) Example F24 includes the subject matter of any of Examples F1-23, and further specifies that the cavity extends past surface insulation material at the face of the substrate.

(716) Example F25 includes the subject matter of any of Examples F1-24, and further specifies that a bottom of the cavity has an undulating surface.

(717) Example F26 includes the subject matter of Example F25, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(718) Example F27 includes the subject matter of Example F25, and further specifies that the undulations have an amplitude that is less than 1 micron.

(719) Example F28 includes the subject matter of any of Examples F1-27, and further specifies that the surface insulation material has a thickness between 10 microns and 30 microns.

(720) Example F29 includes the subject matter of any of Examples F1-28, and further specifies that the bridge component includes a semiconductor material.

(721) Example F30 includes the subject matter of any of Examples F1-29, and further specifies that the bridge component has a thickness that is less than 100 microns.

(722) Example F31 is a microelectronic assembly, including: a substrate; a cavity at a face of the substrate; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, the bridge component includes a first conductive contact at the first face of the bridge component, the bridge component includes a second conductive contact at the second face of the bridge component, and the substrate includes a third conductive contact at a bottom of the cavity; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, a fourth conductive contact of the microelectronic component is conductively coupled to a fifth conductive contact of the substrate at the face of the substrate, and a sixth conductive contact of the microelectronic component is conductively coupled to the first conductive contact at the first face of the bridge component; a first interconnect material between the first conductive contact and the sixth conductive contact; and a second interconnect material between the second conductive contact and the third conductive contact, wherein the second interconnect material has a different melting point than the first interconnect material.

(723) Example F32 includes the subject matter of Example F31, and further specifies that the first interconnect material includes solder.

(724) Example F33 includes the subject matter of Example F32, and further specifies that the solder of the first interconnect material is a first solder, the second interconnect material includes a second solder, and the second solder has a different material composition than the first solder.

(725) Example F34 includes the subject matter of Example F33, and further specifies that the first solder has a lower indium content than the second solder.

(726) Example F35 includes the subject matter of any of Examples F33-34, and further specifies that the first solder has a higher melting point than the second solder.

(727) Example F36 includes the subject matter of any of Examples F33-35, and further specifies that the first solder has a melting point above 200 degrees Celsius, and the second solder has a melting point below 200 degrees Celsius.

(728) Example F37 includes the subject matter of any of Examples F31-36, and further includes: a polymer material around the second interconnect material.

(729) Example F38 includes the subject matter of any of Examples F31-37, and further includes: an epoxy material between the second face of the bridge component and the cavity.

(730) Example F39 includes the subject matter of Example F38, and further specifies that the epoxy material includes an epoxy flux dot.

(731) Example F40 includes the subject matter of Example F38, and further specifies that the epoxy material includes an epoxy flux film.

(732) Example F41 includes the subject matter of any of Examples F31-32, and further specifies that the second interconnect material includes a conductive adhesive, and the conductive adhesive includes a polymer.

(733) Example F42 includes the subject matter of any of Examples F31-32, and further specifies that the second interconnect material includes an intermetallic compound (IMC).

(734) Example F43 includes the subject matter of Example F42, and further specifies that the IMC includes high-temperature solder particles and low-temperature solder particles.

(735) Example F44 includes the subject matter of any of Examples F31-32, and further specifies that the second interconnect material includes a transient liquid phase sintering (TLPS) material.

(736) Example F45 includes the subject matter of any of Examples F31-32 and 44, and further specifies that the second interconnect material includes a polymer, copper, and tin.

(737) Example F46 includes the subject matter of any of Examples F31-45, and further specifies that the substrate includes an organic dielectric material.

(738) Example F47 includes the subject matter of any of Examples F31-46, and further specifies that the substrate includes a conductive contact at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(739) Example F48 includes the subject matter of Example F47, and further includes: solder on the conductive contact of the substrate.

(740) Example F49 includes the subject matter of any of Examples F47-48, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(741) Example F50 includes the subject matter of Example F49, and further specifies that the second conductive contact is a second-level interconnect contact.

(742) Example F51 includes the subject matter of any of Examples F31-50, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(743) Example F52 includes the subject matter of any of Examples F31-51, and further includes: a conductive contact at a bottom of the cavity, wherein the second conductive contact of the bridge component is coupled to the conductive contact by the second interconnect material.

(744) Example F53 includes the subject matter of Example F52, and further specifies that the conductive contact is part of an N-1 metal layer of the substrate.

(745) Example F54 includes the subject matter of any of Examples F31-53, and further specifies that the cavity extends past surface insulation material at the face of the substrate.

(746) Example F55 includes the subject matter of any of Examples F31-54, and further specifies that a bottom of the cavity has an undulating surface.

(747) Example F56 includes the subject matter of Example F55, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(748) Example F57 includes the subject matter of Example F55, and further specifies that the undulations have an amplitude that is less than 1 micron.

(749) Example F58 includes the subject matter of any of Examples F31-57, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(750) Example F59 includes the subject matter of any of Examples F31-58, and further specifies that the bridge component includes a semiconductor material.

(751) Example F60 includes the subject matter of any of Examples F31-59, and further specifies that the bridge component has a thickness that is less than 100 microns.

(752) Example F61 includes the subject matter of any of Examples F31-60, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(753) Example F62 includes the subject matter of any of Examples F31-61, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(754) Example F63 includes the subject matter of any of Examples F31-62, and further specifies that the microelectronic component includes a die.

(755) Example F64 includes the subject matter of any of Examples F31-63, and further includes: a fill compound between the microelectronic component and the substrate.

(756) Example F65 includes the subject matter of Example F64, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(757) Example F66 includes the subject matter of any of Examples F31-65, and further specifies that the microelectronic component includes a transistor.

(758) Example F67 includes the subject matter of any of Examples F31-66, and further specifies that the microelectronic component includes a memory device.

(759) Example F68 includes the subject matter of any of Examples F31-67, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(760) Example F69 includes the subject matter of any of Examples F31-68, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(761) Example F70 includes the subject matter of Example F69, and further specifies that the surface finish further includes palladium and gold.

(762) Example F71 is an electronic device, including: a circuit board; and a microelectronic assembly conductively coupled to the circuit board, wherein the microelectronic assembly includes: a substrate; a cavity at a face of the substrate; a bridge component in the cavity, wherein some of the conductive contacts of the bridge component are coupled to conductive contacts of the substrate; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are coupled to conductive contacts of the substrate, and some of the conductive contacts of the microelectronic component are coupled to conductive contacts of the bridge component; wherein some of the conductive contacts of the bridge component are coupled to conductive contacts of the substrate by second interconnect material, and some of the conductive contacts of the microelectronic component are coupled to conductive contacts of the bridge component by first interconnect material.

(763) Example F72 includes the subject matter of Example F71, and further specifies that the first interconnect material includes solder.

(764) Example F73 includes the subject matter of Example F72, and further specifies that the solder of the first interconnect material is a first solder, the second interconnect material includes a

second solder, and the second solder has a different material composition than the first solder.

(765) Example F74 includes the subject matter of Example F73, and further specifies that the first solder has a different melting point than the second solder.

(766) Example F75 includes the subject matter of any of Examples F73-74, and further specifies that the first solder has a higher melting point than the second solder.

(767) Example F76 includes the subject matter of any of Examples F73-75, and further specifies that the first solder has a melting point above 200 degrees Celsius, and the second solder has a melting point below 200 degrees Celsius.

(768) Example F77 includes the subject matter of any of Examples F71-76, and further includes: a polymer material around the second interconnect material.

(769) Example F78 includes the subject matter of any of Examples F71-77, and further includes: an epoxy material between the second face of the bridge component and the cavity.

(770) Example F79 includes the subject matter of Example F78, and further specifies that the epoxy material includes an epoxy flux dot.

(771) Example F80 includes the subject matter of Example F78, and further specifies that the epoxy material includes an epoxy flux film.

(772) Example F81 includes the subject matter of any of Examples F71-72, and further specifies that the second interconnect material includes a conductive adhesive, and the conductive adhesive includes a polymer.

(773) Example F82 includes the subject matter of any of Examples F71-72, and further specifies that the second interconnect material includes an intermetallic compound (IMC).

(774) Example F83 includes the subject matter of Example F82, and further specifies that the IMC includes high-temperature solder particles and low-temperature solder particles.

(775) Example F84 includes the subject matter of any of Examples F71-72, and further specifies that the second interconnect material includes a transient liquid phase sintering (TLPS) material.

(776) Example F85 includes the subject matter of any of Examples F71-72 and 84, and further specifies that the second interconnect material includes a polymer, copper, and tin.

(777) Example F86 includes the subject matter of any of Examples F71-85, and further specifies that the substrate includes an organic dielectric material.

(778) Example F87 includes the subject matter of any of Examples F71-86, and further specifies that the substrate includes a conductive contact at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(779) Example F88 includes the subject matter of Example F87, and further includes: solder on the conductive contact of the substrate.

(780) Example F89 includes the subject matter of any of Examples F87-88, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(781) Example F90 includes the subject matter of Example F89, and further specifies that the second conductive contact is a second-level interconnect contact.

(782) Example F91 includes the subject matter of any of Examples F71-90, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(783) Example F92 includes the subject matter of any of Examples F71-91, and further includes: a conductive contact at a bottom of the cavity, wherein the second conductive contact of the bridge component is coupled to the conductive contact by the second interconnect material.

(784) Example F93 includes the subject matter of Example F92, and further specifies that the conductive contact is part of an N-1 metal layer of the substrate.

(785) Example F94 includes the subject matter of any of Examples F71-93, and further specifies

that the cavity extends past surface insulation material at the face of the substrate.

(786) Example F95 includes the subject matter of any of Examples F71-94, and further specifies that a bottom of the cavity has an undulating surface.

(787) Example F96 includes the subject matter of Example F95, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(788) Example F97 includes the subject matter of Example F95, and further specifies that the undulations have an amplitude that is less than 1 micron.

(789) Example F98 includes the subject matter of any of Examples F71-97, and further specifies that surface insulation material at the face of the substrate has a thickness between 10 microns and 30 microns.

(790) Example F99 includes the subject matter of any of Examples F71-98, and further specifies that the bridge component includes a semiconductor material.

(791) Example F100 includes the subject matter of any of Examples F71-99, and further specifies that the bridge component has a thickness that is less than 100 microns.

(792) Example F101 includes the subject matter of any of Examples F71-100, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(793) Example F102 includes the subject matter of any of Examples F71-101, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(794) Example F103 includes the subject matter of any of Examples F71-102, and further specifies that the microelectronic component includes a die.

(795) Example F104 includes the subject matter of any of Examples F71-103, and further includes: a fill compound between the microelectronic component and the substrate.

(796) Example F105 includes the subject matter of Example F104, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(797) Example F106 includes the subject matter of any of Examples F71-105, and further specifies that the microelectronic component includes a transistor.

(798) Example F107 includes the subject matter of any of Examples F71-106, and further specifies that the microelectronic component includes a memory device.

(799) Example F108 includes the subject matter of any of Examples F71-107, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(800) Example F109 includes the subject matter of any of Examples F71-108, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(801) Example F110 includes the subject matter of Example F109, and further specifies that the surface finish further includes palladium and gold.

(802) Example F111 includes the subject matter of any of Examples F71-110, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(803) Example F112 includes the subject matter of any of Examples F71-111, and further specifies that the circuit board is a motherboard.

(804) Example F113 includes the subject matter of any of Examples F71-112, and further includes:

a display communicatively coupled to the circuit board.

(805) Example F114 includes the subject matter of Example F113, and further specifies that the display includes a touchscreen display.

(806) Example F115 includes the subject matter of any of Examples F71-114, and further includes: a housing around the circuit board and the microelectronic assembly.

(807) Example G1 is a microelectronic structure, including: a substrate; a cavity in the substrate, wherein metal of a first metal layer in the substrate, and metal of a second metal layer in the substrate, are exposed in the cavity; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, the bridge component includes a conductive contact at the first face of the bridge component, the bridge component includes a second conductive contact at the second face of the bridge component, the second conductive contact is electrically coupled to metal of the first metal layer or the first metal layer, and a portion of the first metal layer is between the bridge component and the second metal layer.

(808) Example G2 includes the subject matter of Example G1, and further specifies that the second conductive contact is electrically coupled to metal of the first metal layer.

(809) Example G3 includes the subject matter of Example G2, and further specifies that metal of the first metal layer and the second metal layer together provide a bottom of the cavity.

(810) Example G4 includes the subject matter of Example G2, and further specifies that the substrate further includes a third metal layer, a portion of the second metal layer is between the bridge component and the third metal layer, and metal of the first metal layer, the second metal layer, and the third metal layer together provide a bottom of the cavity.

(811) Example G5 includes the subject matter of Example G1, and further specifies that the second conductive contact is electrically coupled to metal of the second metal layer.

(812) Example G6 includes the subject matter of Example G5, and further specifies that metal of the first metal layer and the second metal layer together provide a bottom of the cavity.

(813) Example G7 includes the subject matter of any of Examples G1-6, and further specifies that the substrate includes an organic dielectric material.

(814) Example G8 includes the subject matter of any of Examples G1-7, and further specifies that the substrate includes a conductive contact at the face of the substrate, a surface insulation material is at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(815) Example G9 includes the subject matter of Example G8, and further includes: solder on the conductive contact of the substrate.

(816) Example G10 includes the subject matter of any of Examples G8-9, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(817) Example G11 includes the subject matter of Example G10, and further specifies that the second conductive contact is a second-level interconnect contact.

(818) Example G12 includes the subject matter of any of Examples G1-11, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(819) Example G13 includes the subject matter of any of Examples G1-12, and further specifies that a bottom of the cavity has an undulating surface.

(820) Example G14 includes the subject matter of Example G13, and further specifies that the undulations have an amplitude between 1 micron and 10 microns.

(821) Example G15 includes the subject matter of Example G13, and further specifies that the undulations have an amplitude that is less than 1 micron.

(822) Example G16 includes the subject matter of any of Examples G1-15, and further specifies that a surface insulation material is at the face of the substrate, and the surface insulation material has a thickness between 10 microns and 30 microns.

(823) Example G17 includes the subject matter of any of Examples G1-16, and further specifies that the bridge component includes a semiconductor material.

(824) Example G18 includes the subject matter of any of Examples G1-17, and further specifies that the bridge component has a thickness that is less than 100 microns.

(825) Example G19 is a microelectronic structure, including: a substrate; a cavity in the substrate, a bottom of the cavity includes dielectric material and metal; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, the second face of the bridge component is between the first face of the bridge component and the substrate, the bridge component includes a conductive contact at the first face of the bridge component, the bridge component includes a second conductive contact at the second face of the bridge component, the second conductive contact is electrically coupled to metal at a bottom of the cavity.

(826) Example G20 includes the subject matter of Example G19, and further specifies that a top surface of the metal at the bottom of the cavity is coplanar with a top surface of the dielectric material at the bottom of the cavity.

(827) Example G21 includes the subject matter of Example G20, and further specifies that the substrate includes a metal ring at a perimeter of a bottom of the cavity.

(828) Example G22 includes the subject matter of Example G21, and further specifies that the metal ring is coplanar with the metal at the bottom of the cavity.

(829) Example G23 includes the subject matter of Example G19, and further specifies that a top surface of the metal at the bottom of the cavity is non-coplanar with a top surface of the dielectric material at the bottom of the cavity.

(830) Example G24 includes the subject matter of Example G23, and further specifies that a bottom surface of the metal at the bottom of the cavity is coplanar with a top surface of the dielectric material at the bottom of the cavity.

(831) Example G25 includes the subject matter of any of Examples G19-24, and further specifies that the second conductive contact is electrically coupled to metal at the bottom of the cavity by solder.

(832) Example G26 includes the subject matter of any of Examples G19-25, and further specifies that the substrate includes an organic dielectric material.

(833) Example G27 includes the subject matter of any of Examples G19-26, and further specifies that the substrate includes a conductive contact at the face of the substrate, the surface insulation material includes an opening, and the conductive contact of the substrate is at a bottom of the opening.

(834) Example G28 includes the subject matter of Example G27, and further includes: solder on the conductive contact of the substrate.

(835) Example G29 includes the subject matter of any of Examples G27-28, and further specifies that the conductive contact of the substrate is a first conductive contact of the substrate, the face of the substrate is a first face of the substrate, the substrate further includes a second face of the substrate opposite to the first face of the substrate, and the substrate further includes a second conductive contact at the second face of the substrate.

(836) Example G30 includes the subject matter of Example G29, and further specifies that the second conductive contact is a second-level interconnect contact.

(837) Example G31 includes the subject matter of any of Examples G19-30, and further specifies that the cavity is tapered, narrowing towards a bottom of the cavity.

(838) Example G32 includes the subject matter of any of Examples G19-31, and further specifies that a bottom of the cavity has an undulating surface.

(839) Example G33 includes the subject matter of Example G32, and further specifies that the

undulations have an amplitude between 1 micron and 10 microns.

(840) Example G34 includes the subject matter of Example G32, and further specifies that the undulations have an amplitude that is less than 1 micron.

(841) Example G35 includes the subject matter of any of Examples G19-34, and further specifies that the surface insulation material has a thickness between 10 microns and 30 microns.

(842) Example G36 includes the subject matter of any of Examples G19-35, and further specifies that the bridge component includes a semiconductor material.

(843) Example G37 includes the subject matter of any of Examples G19-36, and further specifies that the bridge component has a thickness that is less than 100 microns.

(844) Example G38 is a microelectronic assembly, including: a substrate; a microelectronic structure, including a bridge component in a cavity of a substrate, in accordance with any of Examples G1-37; and a microelectronic component having a first face and an opposing second face, the first face of the microelectronic component is between the second face of the microelectronic component and the substrate, the microelectronic component includes conductive contacts at the first face of the microelectronic component, some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the microelectronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(845) Example G39 includes the subject matter of Example G38, and further specifies that a pitch of conductive contacts of the substrate is greater than a pitch of conductive contacts of the bridge component.

(846) Example G40 includes the subject matter of any of Examples G38-39, and further specifies that the microelectronic component is a first electronic component, and the microelectronic assembly further includes: a second electronic component having a first face and an opposing second face, the first face of the second electronic component is between the second face of the second electronic component and the substrate, the second electronic component includes conductive contacts at the first face of the second electronic component, some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts of the substrate at the face of the substrate, and some of the conductive contacts of the second electronic component are conductively coupled to conductive contacts at the first face of the bridge component.

(847) Example G41 includes the subject matter of any of Examples G38-40, and further specifies that the microelectronic component includes a die.

(848) Example G42 includes the subject matter of any of Examples G38-41, and further includes: a fill compound between the microelectronic component and the substrate.

(849) Example G43 includes the subject matter of Example G42, and further specifies that the fill compound extends between the microelectronic component and the bridge component.

(850) Example G44 includes the subject matter of any of Examples G38-43, and further specifies that the microelectronic component includes a transistor.

(851) Example G45 includes the subject matter of any of Examples G38-44, and further specifies that the microelectronic component includes a memory device.

(852) Example G46 includes the subject matter of any of Examples G38-45, and further specifies that the microelectronic assembly has a footprint that is less than 100 square millimeters.

(853) Example G47 includes the subject matter of any of Examples G38-46, and further specifies that conductive contacts of the substrate include a surface finish, and the surface finish includes nickel.

(854) Example G48 includes the subject matter of Example G47, and further specifies that the surface finish further includes palladium and gold.

(855) Example G49 includes the subject matter of any of Examples G38-48, and further specifies that the substrate includes one or more metal layers above the cavity.

(856) Example G50 includes the subject matter of any of Examples G38-49, and further specifies that the bridge component is embedded in the substrate.

(857) Example G51 is an electronic device, including: a circuit board; and a microelectronic assembly, in accordance with any of the microelectronic assemblies of any of Examples G38-48, conductively coupled to the circuit board.

(858) Example G52 includes the subject matter of Example G51, and further specifies that the electronic device is a handheld computing device, a laptop computing device, a wearable computing device, or a server computing device.

(859) Example G53 includes the subject matter of any of Examples G51-52, and further specifies that the circuit board is a motherboard.

(860) Example G54 includes the subject matter of any of Examples G51-53, and further includes: a display communicatively coupled to the circuit board.

(861) Example G55 includes the subject matter of Example G54, and further specifies that the display includes a touchscreen display.

(862) Example G56 includes the subject matter of any of Examples G51-55, and further includes: a housing around the circuit board and the microelectronic assembly.

Claims

1. A microelectronic structure, comprising: a substrate including a first metal layer and a second metal layer; a cavity in the substrate, wherein a portion of the first metal layer in the substrate, and a portion of the second metal layer in the substrate, are exposed in the cavity, and wherein the portion of the first metal layer at least partially overlaps the portion of the second metal layer; and a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, wherein the second face of the bridge component is between the first face of the bridge component and a bottom surface of the cavity in the substrate, wherein the portion of the first metal layer is between the second face of the bridge component and the portion of the second metal layer, wherein the bridge component includes a first conductive contact at the first face and a second conductive contact at the second face, and wherein the second conductive contact is directly coupled to the portion of the second metal layer in the cavity by solder.
2. The microelectronic structure of claim 1, wherein the portion of the first metal layer and the portion of the second metal layer together provide the bottom surface of the cavity.
3. The microelectronic structure of claim 1, wherein the portion of the first metal layer includes a metal ring around a perimeter of the cavity.
4. The microelectronic structure of claim 1, wherein the second conductive contact is electrically coupled to the portion of the second metal layer by solder.
5. The microelectronic structure of claim 1, further comprising: a microelectronic component electrically coupled to the first conductive contact at the first face of the bridge component.
6. The microelectronic structure of claim 5, wherein the substrate further includes a third conductive contact outside the cavity and the microelectronic component is electrically coupled to the third conductive contact of the substrate.
7. The microelectronic structure of claim 6, wherein the microelectronic component is electrically coupled to the third conductive contact of the substrate by solder.
8. The microelectronic structure of claim 1, further comprising: an underfill material between the second face of the bridge component and the bottom surface of the cavity.
9. A microelectronic assembly, comprising: a substrate including a first metal layer and a second metal layer, wherein a face of the substrate includes first conductive contacts; a cavity in the substrate, wherein a portion of the first metal layer in the substrate, and a portion of the second metal layer in the substrate, are exposed in the cavity, and wherein the portion of the first metal layer at least partially overlaps the portion of the second metal layer; a bridge component in the

cavity, wherein the bridge component includes a first face and an opposing second face, wherein the second face of the bridge component is between the first face of the bridge component and a bottom surface of the cavity in the substrate, wherein the portion of the first metal layer is between the second face of the bridge component and the portion of the second metal layer, wherein the bridge component includes second conductive contacts at the first face and a third conductive contact at the second face, and wherein the third conductive contact is directly coupled to the portion of the second metal layer by solder; and a microelectronic component having a face including fourth conductive contacts, wherein some of the fourth conductive contacts of the microelectronic component are conductively coupled to the first conductive contacts of the substrate, and wherein some of the fourth conductive contacts of the microelectronic component are conductively coupled to the second conductive contacts at the first face of the bridge component.

10. The microelectronic assembly of claim 9, wherein a pitch of first conductive contacts of the substrate is greater than a pitch of second conductive contacts of the bridge component.

11. The microelectronic assembly of claim 9, wherein the microelectronic component is a first microelectronic component, and the microelectronic assembly further comprises: a second microelectronic component having a face including fifth conductive contacts, wherein some of the fifth conductive contacts of the second microelectronic component are conductively coupled to first conductive contacts of the substrate, and wherein some of the fifth conductive contacts of the second microelectronic component are conductively coupled to second conductive contacts at the first face of the bridge component.

12. The microelectronic assembly of claim 9, wherein the microelectronic component includes a die.

13. The microelectronic assembly of claim 9, further comprising: a fill compound between the microelectronic component and the substrate.

14. The microelectronic assembly of claim 9, wherein the microelectronic component includes a transistor.

15. The microelectronic assembly of claim 9, wherein the microelectronic assembly has a footprint that is less than 100 square millimeters.

16. A microelectronic assembly, comprising: a substrate including a first metal layer and a second metal layer, wherein a face of the substrate includes first conductive contacts; a cavity in the substrate, wherein a portion of the first metal layer in the substrate, and a portion of the second metal layer in the substrate, are exposed in the cavity, and wherein the portion of the first metal layer at least partially overlaps the portion of the second metal layer; a bridge component in the cavity, wherein the bridge component includes a first face and an opposing second face, wherein the second face of the bridge component is between the first face of the bridge component and a bottom surface of the cavity in the substrate, wherein the portion of the first metal layer is between the second face of the bridge component and the portion of the second metal layer, wherein the bridge component includes second conductive contacts at the first face and a third conductive contact at the second face, and wherein the third conductive contact is directly coupled to the portion of the second metal layer by solder; a first microelectronic component having a face including fourth conductive contacts, wherein some of the fourth conductive contacts of the first microelectronic component are conductively coupled to the first conductive contacts of the substrate, and wherein some of the fourth conductive contacts of the first microelectronic component are conductively coupled to the second conductive contacts at the first face of the bridge component; and a second microelectronic component having a face including fifth conductive contacts, wherein some of the fifth conductive contacts of the second microelectronic component are conductively coupled to first conductive contacts of the substrate, and wherein some of the fifth conductive contacts of the second microelectronic component are conductively coupled to second conductive contacts at the first face of the bridge component.

17. The microelectronic assembly of claim 16, wherein a pitch of first conductive contacts of the substrate is greater than a pitch of second conductive contacts of the bridge component.
18. The microelectronic assembly of claim 16, further comprising: an underfill material between the second face of the bridge component and the bottom surface of the cavity.
19. The microelectronic assembly of claim 16, further comprising: a fill compound between the first microelectronic component and the substrate and between the second microelectronic component and the substrate.
20. The microelectronic assembly of claim 16, wherein the bridge component has a thickness that is a non-zero value of less than 100 microns.
-