

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12414357
B2
September 09, 2025
Chen; Guan-Lin et al.

Self-aligned metal gate for multigate device

Abstract

Self-aligned gate cutting techniques for multigate devices are disclosed herein that provide multigate devices having asymmetric metal gate profiles and asymmetric source/drain feature profiles. An exemplary multigate device has a channel layer, a metal gate that wraps a portion of the channel layer, and source/drain features disposed over a substrate. The channel layer extends along a first direction between the source/drain features. A first dielectric fin and a second dielectric fin are disposed over the substrate and configured differently. The channel layer extends along a second direction between the first dielectric fin and the second dielectric fin. The metal gate is disposed between the channel layer and the second dielectric fin. In some embodiments, the first dielectric fin is disposed on a first isolation feature, and the second dielectric fin is disposed on a second isolation feature. The first isolation feature and the second isolation feature are configured differently.

Inventors: Chen; Guan-Lin (Hsinchu County, TW), Wang; Chih-Hao (Hsinchu County, TW), Tsai; Ching-Wei (Hsinchu, TW), Ju; Shi Ning (Hsinchu, TW), Huang; Jui-Chien (Hsinchu, TW), Chiang; Kuo-Cheng (Hsinchu County, TW), Cheng; Kuan-Lun (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsin-Chu, TW)

Family ID: 78243201

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING CO., LTD. (Hsinchu, TW)

Appl. No.: 18/752112

Filed: June 24, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240347391 A1	Oct. 17, 2024

Related U.S. Application Data

continuation parent-doc US 18305637 20230424 US 12033899 child-doc US 18752112
continuation parent-doc US 17174109 20210211 US 11637042 20230425 child-doc US 18305637
us-provisional-application US 63017717 20200430

Publication Classification

Int. Cl.: **H01L21/8238** (20060101); **H01L21/02** (20060101); **H01L21/28** (20250101);
H01L27/092 (20060101); **H01L29/06** (20060101); **H01L29/423** (20060101);
H01L29/66 (20060101); **H01L29/786** (20060101); **H10D30/01** (20250101); **H10D30/67**
(20250101); **H10D62/10** (20250101); **H10D84/01** (20250101); **H10D84/03** (20250101);
H10D84/85 (20250101)

U.S. Cl.:

CPC **H10D84/038** (20250101); **H01L21/02603** (20130101); **H01L21/28123** (20130101);
H10D30/031 (20250101); **H10D30/6713** (20250101); **H10D30/6735** (20250101);
H10D30/6757 (20250101); **H10D62/115** (20250101); **H10D62/121** (20250101);
H10D84/0167 (20250101); **H10D84/0172** (20250101); **H10D84/0188** (20250101);
H10D84/85 (20250101);

Field of Classification Search

CPC: H10D (84/038); H10D (30/031); H10D (30/6713); H10D (30/6735); H10D (30/6757);
H10D (62/115); H10D (62/121); H10D (84/0167); H10D (84/0172); H10D (84/0188);
H10D (84/85); H10D (64/252); H10D (84/201); H10D (62/221); H10D (84/135); H10D
(18/60); H10D (48/071); H10D (62/052); H10D (84/144); H10D (84/903); H01L
(21/02603); H01L (21/28123); B65D (83/141); A61K (40/13); A61K (40/4218); A23B
(2/783); A23B (11/29); H02K (15/027); H10H (20/826); H10H (20/851); A01G (13/33);
B82Y (10/00); H10F (77/955)

USPC: 257/351

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6287904	12/2000	Lee et al.	N/A	N/A
11616062	12/2022	Ju et al.	N/A	N/A
11637042	12/2022	Chen et al.	N/A	N/A
2019/0067417	12/2018	Ching et al.	N/A	N/A
2019/0393352	12/2018	Guha et al.	N/A	N/A
2020/0006577	12/2019	Ching et al.	N/A	N/A
2020/0091145	12/2019	Guha et al.	N/A	N/A
2020/0105581	12/2019	Chang et al.	N/A	N/A
2020/0287015	12/2019	Subramanian et al.	N/A	N/A
2021/0265508	12/2020	Chiang	N/A	H01L 29/775
2021/0375858	12/2020	Chiang et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
110556374	12/2018	CN	N/A
102017126106	12/2019	DE	N/A
20180000518	12/2015	KR	N/A
20180079160	12/2017	KR	N/A
20190064514	12/2018	KR	N/A
201926684	12/2018	TW	N/A
2000060659	12/1999	WO	N/A
2016099570	12/2013	WO	N/A
2015094305	12/2014	WO	N/A

Primary Examiner: Kim; Tong-Ho

Attorney, Agent or Firm: HAYNES AND BOONE, LLP

Background/Summary

(1) This application is a continuation application of U.S. patent application Ser. No. 18/305,637, filed Apr. 24, 2023, which is a continuation application of U.S. patent application Ser. No. 17/174,109, filed Feb. 11, 2021, which is a non-provisional application of and claims benefit of U.S. Provisional Patent Application Ser. No. 63/017,717, filed Apr. 30, 2020, the entire disclosures of which are incorporated herein by reference.

BACKGROUND

(1) The electronics industry has experienced an ever-increasing demand for smaller and faster electronic devices that are simultaneously able to support a greater number of increasingly complex and sophisticated functions. To meet these demands, there is a continuing trend in the integrated circuit (IC) industry to manufacture low-cost, high-performance, and low-power ICs. Thus far, these goals have been achieved in large part by reducing IC dimensions (for example, minimum IC feature size), thereby improving production efficiency and lowering associated costs. However, such scaling has also increased complexity of the IC manufacturing processes. Thus, realizing continued advances in IC devices and their performance requires similar advances in IC manufacturing processes and technology.

(2) Recently, multigate devices have been introduced to improve gate control. Multigate devices have been observed to increase gate-channel coupling, reduce OFF-state current, and/or reduce short-channel effects (SCEs). One such multigate device is the gate-all around (GAA) device, which includes a gate structure that can extend, partially or fully, around a channel region to provide access to the channel region on at least two sides. GAA devices enable aggressive scaling down of IC technologies, maintaining gate control and mitigating SCEs, while seamlessly integrating with conventional IC manufacturing processes. However, as GAA devices continue to scale, non-self-aligned gate cutting techniques typically implemented to isolate gates of different GAA devices from one another, such as a first gate of a first GAA transistor from a second gate of a second GAA transistor, are hindering the dense packing of IC features needed for advanced IC technology nodes. Accordingly, although existing GAA devices and methods for fabricating such have been generally adequate for their intended purposes, they have not been entirely satisfactory in all respects.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The present disclosure is best understood from the following detailed description when read with the accompanying figures. It is emphasized that, in accordance with the standard practice in the industry, various features are not drawn to scale and are used for illustration purposes only. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 is a flow chart of a method for fabricating a multigate device according to various aspects of the present disclosure.

(3) FIGS. 2-28, FIG. 29A, and FIG. 29B are fragmentary perspective views of a multigate device, in portion or entirety, at various fabrication stages (such as those associated with the method in FIG. 1) according to various aspects of the present disclosure.

(4) FIG. 29C and FIG. 29D are fragmentary cross-sectional views of a multigate device, in portion or entirety, at various fabrication stages (such as those associated with the method in FIG. 1) according to various aspects of the present disclosure.

DETAILED DESCRIPTION

(5) The present disclosure relates generally to integrated circuit devices, and more particularly, to metal gate cutting technique for multigate devices.

(6) The following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, spatially relative terms, for example, “lower,” “upper,” “horizontal,” “vertical,” “above,” “over,” “below,” “beneath,” “up,” “down,” “top,” “bottom,” etc. as well as derivatives thereof (e.g., “horizontally,” “downwardly,” “upwardly,” etc.) are used for ease of the present disclosure of one features relationship to another feature. The spatially relative terms are intended to cover different orientations of the device including the features. Furthermore, when a number or a range of numbers is described with “about,” “approximate,” and the like, the term is intended to encompass numbers that are within a reasonable range considering variations that inherently arise during manufacturing as understood by one of ordinary skill in the art. For example, the number or range of numbers encompasses a reasonable range including the number described, such as within $\pm 10\%$ of the number described, based on known manufacturing tolerances associated with manufacturing a feature having a characteristic associated with the number. For example, a material layer having a thickness of “about 5 nm” can encompass a dimension range from 4.5 nm to 5.5 nm where manufacturing tolerances associated with depositing the material layer are known to be $\pm 10\%$ by one of ordinary skill in the art. Still further, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) An exemplary non-self-aligned gate cutting technique can involve forming a mask layer over a gate stack, where the mask layer covers a first portion of the gate stack and a second portion of the gate stack and exposes a third portion of the gate stack via an opening formed in the mask layer. The third portion of the gate stack is disposed between the first portion of the gate stack and the second portion of the gate stack. An etching process is then performed that removes the exposed third portion of the gate stack (including, for example, at least one gate electrode layer and at least

one gate dielectric layer), thereby forming a gate opening between and separating the first portion of the gate stack from the second portion of the gate stack. A gate isolation feature, such as a dielectric layer (for example, a silicon nitride layer), is then formed in the gate opening to provide electrical isolation between the first portion of the gate stack, which may be disposed over a first channel layer of a first GAA device (i.e., first active device area), and the second portion of the gate stack, which may be disposed over a second channel layer of a second GAA device (i.e., second active device area).

(8) A spacing between active device areas, such as the first channel layer and the second channel layer, is intentionally designed larger than necessary to compensate for process variations that arise during the non-self-aligned gate cutting technique. For example, etch loading effects and/or other loading effects may reduce critical dimension uniformity (CDU) across a wafer, such that in some locations, a width of the opening in the mask layer and/or a width of the gate opening may be larger than a target width, which can lead to unintentional exposure and/or damage of the first channel layer, the second channel layer, the first portion of the gate stack, and/or the second portion of the gate stack. In another example, overlay shift arising from lithography processes may result in the opening in the mask layer shifted left or right of its intended position, which can also lead to unintentional exposure and/or damage of the first channel layer, the second channel layer, the first portion of the gate stack, and/or the second portion of the gate stack. The increased spacing required between the active device areas to adequately compensate for such process variations prevents compact packing of active device areas needed for advanced IC technology nodes, thereby reducing pattern density.

(9) The present disclosure thus proposes a self-aligned gate cutting technique for multigate devices that allows for smaller spacing between active device areas compared to spacing required between active device areas for non-self-aligned gate cutting techniques. The proposed self-aligned gate cutting technique also reduces both metal gate dimensions and source/drain feature dimensions, thereby increasing pattern density. It has further been observed that the reduced metal gate dimensions and source/drain feature dimensions reduce parasitic capacitance between a metal gate and source/drain features (Cgd), thereby improving speed and performance of a multigate device. In some embodiments, the proposed self-aligned gate cutting technique provides a multigate device with an asymmetric gate profile, for example, where a channel layer of the multigate device has a first sidewall physically contacting a metal gate of the multigate device and a second sidewall physically contacting a first-type dielectric fin. Where the multigate device is a multigate device, the proposed self-aligned gate cutting technique provides a second-type dielectric fin that separates the first multigate device (in particular, a first metal gate of the first multigate device) from a second multigate device (in particular, a second metal gate of the second multigate device). The second-type dielectric fin is different than the first-type dielectric fin. In some embodiments, the second-type dielectric fin includes a low-k dielectric layer, an oxide layer, and a high-k dielectric layer, whereas the first-type dielectric fin includes a low-k dielectric layer and an oxide layer. In some embodiments, the first-type dielectric fin and the second-type dielectric fin are disposed on differently configured isolation features, such as different shallow trench isolation (STI) features. For example, the first-type dielectric fin is disposed over a first-type isolation feature that includes an oxide layer disposed over a dielectric liner, and the second-type dielectric fin is disposed over a second-type isolation feature that includes an oxide layer (and is free of any dielectric liner). The proposed self-aligned gate cutting technique further provides a third-type dielectric fin that separates first source/drain features of the first multigate device from second source/drain features of the second multigate device. The first source/drain features are further disposed between the third-type dielectric fin and a fourth-type dielectric fin. In some embodiments, the third-type dielectric fin and the fourth-type dielectric fin each include a low-k dielectric layer, an oxide layer, and a high-k dielectric layer. In some embodiments, the third-type dielectric fin is disposed over an isolation feature configured substantially the same as the second-type isolation feature, and the

fourth-type dielectric fin is disposed over an isolation feature configured substantially the same as the first-type isolation feature. In some embodiments, the third-type dielectric fin and the fourth-type dielectric fin are configured similar to the second-type dielectric fin, except that a top surface of the high-k dielectric layer of the second-type dielectric fin relative to a substrate is higher than top surfaces of the third-type dielectric fin and the fourth-type dielectric fin relative to the substrate. The first source/drain features have an asymmetric source/drain profile. In some embodiments, a length of a first sidewall of the first source/drain features physically contacting the third-type dielectric fin is less than a length of a second sidewall of the first source/drain features physically contacting the fourth-type dielectric fin. In some embodiments, a length of first facets of the first source/drain features proximate the third-type dielectric fin is greater than a length of second facets of the first source/drain features proximate the fourth-type dielectric fin. The various dielectric fins, which separate and isolate metal gates, can also be referred to as gate isolation fins, dielectric gate isolation fins, and/or isolation fins. Details of the proposed self-aligned gate cutting technique for multigate devices and resulting multigate devices are described herein in the following pages.

(10) FIG. 1 is a flow chart of a method **100** for fabricating a multigate device according to various aspects of the present disclosure. In some embodiments, method **100** fabricates a p-type multigate transistor and/or an n-type multigate transistor. At block **110**, method **100** includes forming a first isolation feature and a second isolation feature in a substrate. The first isolation feature is different than the second isolation feature. For example, the first isolation feature includes a first oxide layer, a first dielectric liner, and a first silicon liner, and the second isolation feature includes a second oxide layer and a second silicon liner. The second isolation feature is free of a dielectric liner, in some embodiments. At block **115**, method **100** includes forming a first dielectric fin over the first isolation feature and a second dielectric fin over the second isolation feature. The first dielectric fin is different than the second dielectric fin. For example, the first dielectric fin includes a third oxide layer and a first dielectric layer in a channel region of the multigate device, the first dielectric fin includes the third oxide layer, the first dielectric layer, and a second dielectric layer in source/drain regions of the multigate device, and the second dielectric fin includes a fourth oxide layer, a third dielectric layer, and a fourth dielectric layer in the channel region and the source/drain regions of the multigate device. The first dielectric layer and the third dielectric layer have a first dielectric constant, the second dielectric layer and the fourth dielectric layer have a second dielectric constant, and the second dielectric constant is greater than the first dielectric constant. In some embodiments, the dielectric liner of the first isolation feature has the first dielectric constant. In some embodiments, a width of the first dielectric fin is about the same as a width of the first isolation feature, and a width of the second dielectric fin is less than a width of the second isolation feature. In some embodiments, the first dielectric layer and the third dielectric layer include a silicon-comprising dielectric material, and the second dielectric layer and the fourth dielectric layer include a metal-and-oxygen comprising material.

(11) At block **120**, method **100** includes forming a multigate device having a channel layer, a metal gate that wraps a portion of the channel layer, and source/drain features. The channel layer extends along a first direction between the source/drain features and along a second direction between the first dielectric fin and the second dielectric fin. The second direction being different than the first direction. The metal gate is disposed between and separates the channel layer from the second dielectric fin. The metal gate and the source/drain features have asymmetric profiles. In some embodiments, the multigate device is a first multigate device, such as a transistor, disposed in a first multigate device region of an IC device. In such embodiments, the first dielectric fin separates and isolates the metal gate of the first multigate device from a device feature, such as a metal gate, of a second multigate device in the first multigate device region. The first multigate device and the second multigate device may form a complementary transistor in the first multigate device region. In such embodiments, the second dielectric fin separates and isolates the first multigate device from a third multigate device or other type device in a second multigate device region that is disposed

adjacent to the first multigate device region. Additional processing is contemplated by the present disclosure. Additional steps can be provided before, during, and after method **100**, and some of the steps described can be moved, replaced, or eliminated for additional embodiments of method **100**. The discussion that follows illustrates various embodiments of multigate-based integrated circuit devices that can be fabricated according to method **100**.

(12) FIGS. **2-28**, FIG. **29A**, and FIG. **29B** are fragmentary perspective views of a multigate device **200**, in portion or entirety, at various fabrication stages (such as those associated with method **100** in FIG. **1**) according to various aspects of the present disclosure. FIG. **29C** and FIG. **29D** are fragmentary cross-sectional views of multigate device **200**, in portion or entirety, at various fabrication stages (such as those associated with method **100** in FIG. **1**) according to various aspects of the present disclosure. As described herein, multigate device **200** includes an n-type transistor region **202A** processed to form n-type transistors, a p-type transistor region **202B** processed to form p-type transistors, and an n-type transistor region processed to form n-type transistors. As further described herein, n-type transistor region **202A**, p-type transistor region **202B**, and n-type transistor region **202C** are further processed to provide a first multigate device in a first multigate device region **204A** and a second multigate device in a second multigate device region **204B**. The first multigate device includes an n-type transistor (formed in n-type transistor region **202A**) and a p-type transistor (formed in p-type transistor region **202B**) and the second multigate device includes an n-type transistor (formed in n-type transistor region **202C**) and a p-type transistor (formed in p-type transistor region **202B**), such that first multigate device region **204A** and second multigate device region **204B** each include a complementary transistor, such as a complementary metal-oxide semiconductor (CMOS) transistor. In some embodiments, first multigate device region **204A** and second multigate device region **204B** are a portion of a device region, such as a core region (often referred to as a logic region), a memory region (such as a static random access memory (SRAM) region), an analog region, a peripheral region (often referred to as an I/O region), a dummy region, other suitable region, or combinations thereof. The device region can include various passive and active microelectronic devices, such as resistors, capacitors, inductors, diodes, p-type field effect transistors (PFETs), n-type field effect transistors (NFETs), metal-oxide semiconductor field effect transistors (MOSFETs), CMOS transistors, bipolar junction transistors (BJTs), laterally diffused MOS (LDMOS) transistors, high voltage transistors, high frequency transistors, other suitable components, or combinations thereof. Multigate device **200** can be included in a microprocessor, a memory, and/or other IC device. In some embodiments, multigate device **200** is a portion of an IC chip, a system on chip (SoC), or portion thereof. FIGS. **2-28**, FIG. **29A**, FIG. **29B**, FIG. **29C**, and FIG. **29D** have been simplified for the sake of clarity to better understand the inventive concepts of the present disclosure. Additional features can be added in multigate device **200**, and some of the features described below can be replaced, modified, or eliminated in other embodiments of multigate device **200**.

(13) Turning to FIG. **2**, a fin fabrication process is performed to form fins extending from a substrate (wafer) **206**. For example, a fin **208A**, a fin **208B**, a fin **208C**, and a fin **208D** (also referred to as fin structures, fin elements, etc.) extend from substrate **206** after the fin fabrication process. Each of fins **208A-208D** include a substrate portion (i.e., a fin portion **206'** of substrate **206** (also referred to as a substrate extension, a substrate fin portion, an etched substrate portion, etc.)), a semiconductor layer stack portion (i.e., a semiconductor layer stack **210** that includes semiconductor layers **215** and semiconductor layers **220**) disposed over the substrate portion, and a patterning layer portion (i.e., a patterning layer **225** that includes a pad layer **226** and a mask layer **227**) disposed over the semiconductor layer stack portion. Fins **208A-208D** extend substantially parallel to one another along a y-direction, having a length defined in the y-direction, a width defined in an x-direction, and a height defined in a z-direction.

(14) In some embodiments, a lithography and/or etching process is performed to pattern a semiconductor layer stack to form fins **208A-208D**. The lithography process can include forming a

resist layer over semiconductor layer stack **210** (for example, by spin coating), performing a pre-exposure baking process, performing an exposure process using a mask, performing a post-exposure baking process, and performing a developing process. During the exposure process, the resist layer is exposed to radiation energy (such as ultraviolet (UV) light, deep UV (DUV) light, or extreme UV (EUV) light), where the mask blocks, transmits, and/or reflects radiation to the resist layer depending on a mask pattern of the mask and/or mask type (for example, binary mask, phase shift mask, or EUV mask), such that an image is projected onto the resist layer that corresponds with the mask pattern. Since the resist layer is sensitive to radiation energy, exposed portions of the resist layer chemically change, and exposed (or non-exposed) portions of the resist layer are dissolved during the developing process depending on characteristics of the resist layer and characteristics of a developing solution used in the developing process. After development, the patterned resist layer includes a resist pattern that corresponds with the mask. The etching process removes portions of semiconductor layer stack **210** using the patterned resist layer as an etch mask. In some embodiments, the patterned resist layer is formed over a mask layer disposed over semiconductor layer stack **210**, a first etching process removes portions of the mask layer to form patterning layer **225** (i.e., a patterned hard mask layer), and a second etching process removes portions of semiconductor layer stack **210** using patterning layer **225** as an etch mask. The etching process can include a dry etching process, a wet etching process, other suitable etching process, or combinations thereof. In some embodiments, the etching process is a reactive ion etching (RIE) process. After the etching process, the patterned resist layer is removed, for example, by a resist stripping process or other suitable process. Alternatively, fins **208A-208D** are formed by a multiple patterning process, such as a double patterning lithography (DPL) process (for example, a lithography-etch-lithography-etch (LELE) process, a self-aligned double patterning (SADP) process, a spacer-is-dielectric (SID) SADP process, other double patterning process, or combinations thereof), a triple patterning process (for example, a lithography-etch-lithography-etch-lithography-etch (LELELE) process, a self-aligned triple patterning (SATP) process, other triple patterning process, or combinations thereof), other multiple patterning process (for example, self-aligned quadruple patterning (SAQP) process), or combinations thereof. Such processes can also provide fins **208A-208D** with patterning layer **225**, semiconductor layer stack **210**, and fin portion **206'**, as depicted in FIG. 2. In some embodiments, directed self-assembly (DSA) techniques are implemented while patterning semiconductor layer stack **210**. Further, in some embodiments, the exposure process can implement maskless lithography, electron-beam (e-beam) writing, and/or ion-beam writing for patterning the resist layer.

(15) In the depicted embodiment, substrate **206** includes silicon. Alternatively or additionally, substrate **206** includes another elementary semiconductor, such as germanium; a compound semiconductor, such as silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor, such as silicon germanium (SiGe), GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP; or combinations thereof. Alternatively, substrate **206** is a semiconductor-on-insulator substrate, such as a silicon-on-insulator (SOI) substrate, a silicon germanium-on-insulator (SGOI) substrate, or a germanium-on-insulator (GOI) substrate. Semiconductor-on-insulator substrates can be fabricated using separation by implantation of oxygen (SIMOX), wafer bonding, and/or other suitable methods. Substrate **206** can include various doped regions. For example, substrate **206** (including fin portions **206'**) can include p-type doped regions (referred to as p-wells) in n-type transistor regions **202A**, **202C** and n-type doped regions (referred to as n-wells) in p-type transistor region **202B**. The n-wells are doped with n-type dopants, such as phosphorus, arsenic, other n-type dopant, or combinations thereof. The p-wells are doped with p-type dopants, such as boron, indium, other p-type dopant, or combinations thereof. In some embodiments, substrate **206** includes doped regions formed with a combination of p-type dopants and n-type dopants. The various doped regions can be formed directly on and/or in substrate **206**, for example, providing a p-well structure, an n-well structure, a dual-well structure, a

raised structure, or combinations thereof. An ion implantation process, a diffusion process, and/or other suitable doping process can be performed to form the various doped regions.

(16) Each semiconductor layer stack **210** is disposed over a respective fin portion **206'** of substrate **206** and includes semiconductor layers **215** and semiconductor layers **220** stacked vertically (e.g., along the z-direction) in an interleaving or alternating configuration from a top surface of substrate **206**. In some embodiments, semiconductor layers **215** and semiconductor layers **220** are epitaxially grown in the depicted interleaving and alternating configuration. For example, a first one of semiconductor layers **215** is epitaxially grown on substrate **206**, a first one of semiconductor layers **220** is epitaxially grown on the first one of semiconductor layers **220**, a second one of semiconductor layers **215** is epitaxially grown on the first one of semiconductor layers **220**, and so on until semiconductor layer stacks **210** have a desired number of semiconductor layers **215** and semiconductor layers **220**. In such embodiments, semiconductor layers **215** and semiconductor layers **220** can be referred to as epitaxial layers. In some embodiments, epitaxial growth of semiconductor layers **215** and semiconductor layers **220** is achieved by a molecular beam epitaxy (MBE) process, a chemical vapor deposition (CVD) process, a metalorganic chemical vapor deposition (MOCVD) process, other suitable epitaxial growth process, or combinations thereof. A composition of semiconductor layers **215** is different than a composition of semiconductor layers **220** to achieve etching selectivity and/or different oxidation rates during subsequent processing. In some embodiments, semiconductor layers **215** have a first etch rate to an etchant and semiconductor layers **220** have a second etch rate to the etchant, where the second etch rate is different than the first etch rate. In some embodiments, semiconductor layers **215** have a first oxidation rate and semiconductor layers **220** have a second oxidation rate, where the second oxidation rate is different than the first oxidation rate. In the depicted embodiment, semiconductor layers **215** and semiconductor layers **220** include different materials, constituent atomic percentages, constituent weight percentages, thicknesses, and/or characteristics to achieve desired etching selectivity during an etching process, such as an etching process implemented to form suspended channel layers in channel regions of multigate device **200**. For example, where semiconductor layers **215** include silicon germanium and semiconductor layers **220** include silicon, a silicon etch rate of semiconductor layers **220** is less than a silicon germanium etch rate of semiconductor layers **215**. In some embodiments, semiconductor layers **215** and semiconductor layers **220** include the same material but with different constituent atomic percentages to achieve the etching selectivity and/or different oxidation rates. For example, semiconductor layers **215** and semiconductor layers **220** can include silicon germanium, where semiconductor layers **215** have a first silicon atomic percent and/or a first germanium atomic percent and semiconductor layers **220** have a second, different silicon atomic percent and/or a second, different germanium atomic percent. The present disclosure contemplates that semiconductor layers **215** and semiconductor layers **220** include any combination of semiconductor materials that can provide desired etching selectivity, desired oxidation rate differences, and/or desired performance characteristics (e.g., materials that maximize current flow), including any of the semiconductor materials disclosed herein.

(17) As described further below, semiconductor layers **220** or portions thereof form channel regions of multigate device **200**. In the depicted embodiment, each semiconductor layer stack **210** includes three semiconductor layers **215** and three semiconductor layers **220** configured to form three semiconductor layer pairs disposed over substrate **206**, each semiconductor layer pair having a respective semiconductor layer **215** and a respective semiconductor layer **220**. After undergoing subsequent processing, such configuration will result in multigate device **200** having three channels. However, the present disclosure contemplates embodiments where semiconductor layer stack **210** includes more or less semiconductor layers, for example, depending on a number of channels desired for multigate device **200** and/or design requirements of multigate device **200**. For example, semiconductor layer stacks **210** can include two to ten semiconductor layers **215** and two

to ten semiconductor layers **220**. In furtherance of the depicted embodiment, semiconductor layers **215** have a thickness t_1 and semiconductor layers **220** have a thickness t_2 , where thickness t_1 and thickness t_2 are chosen based on fabrication and/or device performance considerations for multigate device **200**. For example, thickness t_1 can be configured to define a desired distance (or gap) between adjacent channels of multigate device **200** (e.g., between semiconductor layers **220**), thickness t_2 can be configured to achieve desired thickness of channels of multigate device **200**, and thickness t_1 and thickness t_2 can be configured to achieve desired performance of multigate device **200**. In some embodiments, semiconductor layers **220** include n-type and/or p-type dopants depending on their corresponding transistor region. For example, semiconductor layers **220** in n-type transistor regions **202A**, **202C** can include p-type dopants and semiconductor layers **220** in p-type transistor region **202B** can include n-type dopants.

(18) A trench **230A** is defined between fin **208A** and fin **208B**, a trench **230B** is defined between fin **208B** and fin **208C**, and a trench **230C** is defined between fin **208C** and fin **208D**. For example, trench **230A** has a sidewall defined by fin **208A**, a sidewall defined by fin **208B**, and a bottom defined by substrate **206** that extends between the sidewalls; trench **230B** has a sidewall defined by fin **208B**, a sidewall defined by fin **208C**, and a bottom defined by substrate **206** that extends between the sidewalls; and trench **230C** has a sidewall defined by fin **208C**, a sidewall defined by fin **208D**, and a bottom defined by substrate **206** that extends between the sidewalls. Turning to FIG. 3, a silicon liner **235** is formed over fins **208A-208D** and substrate **206**, such that silicon liner **235** partially fills trenches **230A-230C**. For example, silicon liner **235** covers substrate **206** and fins **208A-208D**, such that silicon liner **235** covers sidewalls and bottoms of trenches **230A-230C**. In some embodiments, an atomic layer deposition (ALD) process is performed to deposit silicon liner **235** having a thickness t_3 over multigate device **200**. In some embodiments, thickness t_3 is substantially uniform over various surfaces of multigate device **200**. For example, thickness t_3 along sidewalls of trenches **230A-230C** (i.e., over sidewalls of fins **208A-208D**) is substantially the same as thickness t_3 along bottoms of trenches **230A-230C** (i.e., over top surfaces of substrate **206**) and thickness t_3 along top surfaces of fins **208A-208D**. In some embodiments, thickness t_3 is about 1 nm to about 5 nm. In some embodiments, silicon liner **235** is formed by chemical vapor deposition (CVD), physical vapor deposition (PVD), high density plasma CVD (HDPCVD), metal organic CVD (MOCVD), remote plasma CVD (RPCVD), plasma enhanced CVD (PECVD), low-pressure CVD (LPCVD), atomic layer CVD (ALCVD), atmospheric pressure CVD (APCVD), sub-atmospheric vapor deposition (SAVCD), other suitable methods, or combinations thereof. In some embodiments, silicon liner **235** includes n-type dopants and/or p-type dopants.

(19) Turning to FIG. 4, a dielectric liner **240** is formed over silicon liner **235** and partially fills trenches **230A-230C**. For example, dielectric liner **240** covers substrate **206** and fins **208A-208D**, such that dielectric liner **240** covers sidewalls and bottoms of trenches **230A-230C**. In some embodiments, an ALD process is performed to deposit dielectric liner **240** having a thickness t_4 over multigate device **200**. In some embodiments, thickness t_4 is substantially uniform over various surfaces of multigate device **200**. For example, thickness t_4 along sidewalls of trenches **230A-230C** (i.e., over sidewalls of fins **208A-208D**) is substantially the same as thickness t_4 along bottoms of trenches **230A-230C** (i.e., over top surfaces of substrate **206**) and thickness t_4 along top surfaces of fins **208A-208D**. In some embodiments, thickness t_4 is about 2 nm to about 10 nm. In some embodiments, dielectric liner **240** is formed by CVD, PVD, HDPCVD, MOCVD, RPCVD, PECVD, LPCVD, APCVD, SAVCD, other suitable methods, or combinations thereof. Dielectric liner **240** includes a nitrogen-comprising dielectric material, such as a dielectric material that includes nitrogen in combination with silicon, carbon, and/or oxygen, and thus can be referred to as a nitride liner. For example, in some embodiments, dielectric liner **240** includes silicon nitride (SiN), silicon oxynitride (SiON), silicon carbon nitride (SiCN), and/or silicon oxycarbon nitride (SiOCN). In some embodiments, dielectric liner **240** includes n-type dopants and/or p-type dopants.

(20) Turning to FIG. 5, dielectric liner **240** is removed from an interface region between different device regions, such as an interface region between first multigate device region **204A** and second multigate device region **204B**. For example, a lithography process, such as those described herein, is performed to form a patterned mask layer **245** having openings therein that expose interface regions of multigate device **200**. In the depicted embodiment, patterned mask layer **245** includes an opening **247A** that exposes a first interface region between first multigate device region **204A** and second multigate device region **204B**, an opening **247B** that exposes a second interface region between first multigate device region **204A** and another device region (for example, positioned left of first multigate device region **204A**), and an opening **247C** that exposes a third interface region between second multigate device region **204B** and another device region (for example, positioned right of second multigate device region **204B**). The first interface region, exposed by opening **247A**, includes an interface between first multigate device region **204A** and second multigate device region **204B**, a portion of first multigate device region **204A** adjacent to the interface, and a portion of second multigate device region **204B** adjacent to the interface. Opening **247A** thus exposes dielectric liner **240** disposed in trench **230B**, along with a portion of dielectric liner **240** disposed over the top surface of fin **208B** and a portion of dielectric liner **240** disposed over the top surface of fin **208C**. Patterned mask layer **245** includes a mask portion **245A**, which fills trench **230A** and covers an interface region between n-type transistor region **202A** and p-type transistor region **202B**. Mask portion **245A** covers a portion of the top surface of fin **208A** and a portion of the top surface of fin **208B**. Patterned mask layer **245** also includes a mask portion **245B**, which fills trench **230C** and covers an interface region between p-type transistor region **202B** and n-type transistor region **202C**. Mask portion **245B** covers a portion of the top surface of fin **208C** and a portion of the top surface of fin **208D**.

(21) An etching process is then performed to remove dielectric liner **240** from the exposed interface regions, thereby forming a dielectric liner **240A** and a dielectric liner **240B**. The etching process is a dry etching process, a wet etching process, or combination thereof. In the depicted embodiment, the etching process selectively etches dielectric liner **240** with minimal (to no) etch of silicon liner **235**, such that silicon liner **235** remains in trenches at interface regions between different device regions, such as trench **230B** spanning first multigate device region **204A** and second multigate device region **204B**. In FIG. 5, dielectric liner **240A** spans an interface between n-type transistor region **202A** and p-type transistor region **202B** in first multigate device region **204A**, and dielectric liner **240B** spans an interface between p-type transistor region **202B** and n-type transistor region **202C** in second multigate device region **204B**. Dielectric liner **240A** covers sidewalls and bottom of trench **230A** and dielectric liner **240B** covers sidewalls and bottom of trench **230C**. In some embodiments, dielectric liner **240A** covers a portion of the top surface of fin **208A** and a portion of the top surface of fin **208B**, and dielectric liner **240B** covers a portion of the top surface of fin **208C** and a portion of the top surface of fin **208D**. In some embodiments, patterned mask layer **245** is configured such that dielectric liner **240** is removed from the top surfaces of fins **208A-208D**, dielectric liner **240A** is disposed only in trench **230A**, and dielectric liner **240B** is disposed only in trench **230C**. Thereafter, turning to FIG. 6, patterned mask layer **245** (here, mask portion **245A** and mask portion **245B**) is removed from multigate device **200**, for example, by a resist stripping process, an etching process, other suitable process, or combination thereof. Accordingly, silicon liner **235** and dielectric liner **240A** partially fill trench **230A**, silicon liner **235** partially fills trench **230B**, and silicon liner **235** and dielectric liner **240B** partially fill trench **230C**.

(22) Turning to FIG. 7, remainders of trenches **230A-230C** are filled with an oxide material **250**. For example, a deposition process and a planarization process are performed to form oxide material **250** over silicon liner **235**, dielectric liner **240A**, and dielectric liner **240B** and fill any remaining portions of trenches **230A-230C**. In some embodiments, oxide material **250** is deposited by a flowable CVD (FCVD) process that includes, for example, depositing a flowable oxide material (for example, in a liquid state) over multigate device **200** and converting the flowable oxide

material into a solid oxide material by an annealing process. The flowable oxide material can flow into trenches **230A-230C** and conform to exposed surfaces of multigate device **200**, enabling void free filling of trenches **230A-230C**. For example, the FCVD process introduces a silicon-comprising precursor and an oxidizer (collectively referred to as reactants) into a deposition chamber, where the silicon-comprising precursor and the oxidizer react and condense onto exposed surfaces of multigate device **200** (for example, silicon liner **235**, dielectric liner **240A**, and/or dielectric liner **240B**) to form the flowable oxide material. In some embodiments, the flowable oxide material is a flowable silicon-and-oxygen comprising material. In some embodiments, the silicon-containing precursor is a silazene-based precursor (e.g., polysilazane, silylamine, ditrisilylamine, dimethylsilane, trimethylsilane, tetramethylsilane, diethylsilane, other suitable silicon-containing precursor, or combinations thereof) and the oxidizer includes oxygen (e.g., O.sub.2, O.sub.3, hydrogen peroxide (H.sub.2O.sub.2), H.sub.2O, other suitable oxygen-containing constituents, or combinations thereof). In some embodiments, the silicon-containing precursor, such as the silazene-based precursor, is introduced into the deposition chamber in a liquid or vapor state. In some embodiments, the oxidizer is excited to an ionized state by plasma, such that the oxidizer is introduced into the deposition chamber in a plasma state. In some embodiments, the silicon-containing precursor and/or the oxidizer is mixed with a carrier gas (including, for example, hydrogen, helium, argon, nitrogen, xenon, krypton, neon, other suitable constituent, or combinations thereof) before or after introduction into the deposition chamber. In the depicted embodiment, the annealing process converts the flowable silicon-and-oxygen material into a silicon-and-oxygen containing layer, such as a silicon oxide layer. Oxide material **250** may thus be referred to as a silicon oxide layer. In some embodiments, the annealing process is a thermal annealing that heats multigate device **200** to a temperature that can facilitate conversion of the flowable oxide material into the solid oxide material. In some embodiments, the annealing process exposes the flowable oxide material to UV radiation. In some embodiments, oxide material **250** is deposited by a high aspect ratio deposition (HARP) process. The HARP process can implement a TEOS precursor and an O.sub.3 precursor. In some embodiments, oxide material **250** is deposited by HDPCVD. The HDPCVD can implement an SiH.sub.4 precursor and an O.sub.2 precursor. The present disclosure contemplates implementing other deposition processes and/or precursors to deposit oxide material **250**.

(23) The deposition process overfills trenches **230A-230C**, such that a thickness of oxide material **250** is greater than a height of fins **208A-208D**. After the deposition process, the planarization process, such as a chemical mechanical polishing (CMP) process, is performed on oxide material **250**, thereby reducing the thickness of oxide material **250**. In the depicted embodiment, silicon liner **235** functions as a planarization (e.g., CMP) stop layer, such that the planarization process is performed until reaching and exposing silicon liner **235** that is disposed over top surfaces of fins **208A-208D**. Accordingly, after the planarization process, the thickness of oxide material is substantially equal to a sum of a height of fins **208A-208D** and thickness t_3 of silicon liner **235** disposed over the top surfaces of fins **208A-208D**. The planarization process thus removes any oxide material **250**, dielectric liner **240A**, and dielectric liner **240B** that is disposed over the top surfaces of fins **208A-208D**. In some embodiments, top surfaces of oxide material **250**, dielectric liner **240A**, dielectric liner **240B**, and silicon liner **235** are substantially planar after the planarization process. In some embodiments, an annealing process is subsequently performed to further cure and/or densify oxide material **250**.

(24) Turning to FIG. 8, oxide material **250** is recessed, such that fins **208A-208D** extend (protrude) from between oxide material **250**. For example, oxide material **250** surrounds a bottom portion of fins **208A-208D**, thereby defining upper fin active regions **255U** of fins **208A-208D** (generally referring to a portion of fins **208A-208D** that extends from top surfaces of oxide material **250**) and lower fin active regions **255L** of fins **208A-208D** (generally referring to a portion of fins **208A-208D** surrounded by oxide material **250**, which extend from the top surface of substrate **206** to the

top surfaces of oxide material **250**). In FIG. 8, after recessing oxide material **250**, lower portion of trench **230A** is filled with oxide material **250**, dielectric liner **240A**, and silicon liner **235** while upper portion of trench **230A** is partially filled with dielectric liner **240A** and silicon liner **235**; lower portion of trench **230B** is filled with oxide material **250** and silicon liner **235** while upper portion of trench **230A** is partially filled with silicon liner **235**; and lower portion of trench **230C** is filled with oxide material **250**, dielectric liner **240A**, and silicon liner **235** while upper portion of trench **230C** is partially filled with dielectric liner **240A** and silicon liner **235**. In some embodiments, an etching process recesses oxide material **250** until achieving a desired (target) height of upper fin active regions **255U**. In the depicted embodiment, the etching process proceeds until reaching fin portions **206'** of fins **208A-208D**, such that semiconductor layer stacks **210** define upper fin active regions **255U**. In some embodiments, as depicted, top surfaces of fin portions **206'** are substantially planar with top surfaces of oxide material **250** after the etching process. In some embodiments, fin portions **206'** are partially exposed by the etching process, such that top surfaces of fin portions **206'** are higher than top surfaces of oxide material **250** relative to the top surface of substrate **206** after the etching process. In some embodiments, semiconductor layer stacks **210** are partially, instead of fully exposed, by the etching process, such that top surfaces of fin portions **206'** are lower than top surfaces of oxide material **250** relative to the top surface of substrate **206** after the etching process. The etching process is configured to selectively remove oxide material **250** with respect to silicon liner **235**, dielectric liner **240A**, and dielectric liner **240B**. In other words, the etching process substantially removes oxide material **250** but does not remove, or does not substantially remove, silicon liner **235**, dielectric liner **240A**, and dielectric liner **240B**. For example, an etchant is selected for the etch process that etches silicon oxide (i.e., oxide material **250**) at a higher rate than silicon (i.e., silicon liner **235**) and a silicon-and-nitrogen comprising material (i.e., dielectric liners **240A**, **240B**) (i.e., the etchant has a high etch selectivity with respect to silicon oxide). The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, a dry etching process implements a nitrogen-comprising etch gas, such as NF_3 and NH_3 or NH_3 and HF , to selectively etch silicon oxide (i.e., oxide material **250**) with respect to silicon (i.e., silicon liner **235**) and silicon-and-nitrogen comprising material (i.e., dielectric liner **240A** and dielectric liner **240B**). In some embodiments, the etching process uses a patterned mask layer as an etch mask, where the patterned mask layer covers fins **208A-208D** but has openings that expose oxide material **250**.

(25) Turning to FIG. 9, a silicon germanium sacrificial layer **258** is formed over fins **208A-208D**. In the depicted embodiment, silicon germanium sacrificial layer **258** is formed on top surfaces of fins **208A-208D** and an upper portion of one sidewall of fins **208A-208D**. In furtherance of the depicted embodiment, upper portion of trench **230B** is partially filled with silicon germanium sacrificial layer **258**, while upper portions of trench **230A** and trench **230C** are partially filled by dielectric liner **240A** and dielectric liner **240B**, respectively. Silicon germanium sacrificial layer **258** has a thickness **15** that is greater than thickness **t3** of silicon liner **235**. In some embodiments, thickness **t5** is about 4 nm to about 15 nm. In some embodiments, a deposition process is performed that selectively grows a silicon germanium layer over exposed portions of silicon liner **235** (i.e., semiconductor surfaces) without growing the silicon germanium layer on exposed portions of dielectric liner **240A**, dielectric liner **240B**, and oxide material **250** (e.g., dielectric surfaces), where thermal conditions (e.g., growth temperatures) of the deposition process or a thermal process (e.g., an annealing process) performed after the deposition process drives (diffuses) germanium from the silicon germanium layer into the exposed portions of silicon liner **235**, thereby causing the exposed portions of the silicon liner **235** to become a part of the silicon germanium layer. In some embodiments, the deposition process is an epitaxy process that uses CVD deposition techniques (for example, LPCVD, VPE, and/or UHV-CVD), molecular beam epitaxy, other suitable epitaxial growth processes, or combinations thereof. The epitaxy process can use gaseous and/or liquid precursors (e.g., a silane precursor and a germanium precursor), which interact with the

composition of silicon liner **235**. Silicon germanium sacrificial layer **258** can also be referred to as a silicon germanium cladding layer, a silicon germanium helmet, and/or a silicon germanium protection layer.

(26) Turning to FIG. **10**, dielectric liner **240A** and dielectric liner **240B** are removed from upper portions of trenches **230A-230C** by an etching process, thereby forming isolation features **260A** and isolation features **260B**. Isolation features **260A** electrically isolate active device regions and/or passive device regions of multigate device **200** from each other. For example, isolation features **260A** separate and electrically isolate first multigate device region **204A** from second multigate device region **204B**, first multigate device region **204A** from other active device regions and/or passive device regions of multigate device **200**, and second multigate device region **204B** from other active device regions and/or passive device regions of multigate device **200**. In FIG. **10**, one of isolation features **260A** fills lower portion of trench **230B** and is disposed between lower fin active regions **255L** of fins **208B**, **208C**. Isolation features **260B** electrically isolate devices within device regions of multigate device **200** from each other, such as different transistors within a device region. For example, isolation features **260B** separate and electrically isolate n-type transistor region **202A** from p-type transistor region **202B** within first multigate device region **204A** and p-type transistor region **202B** from n-type transistor region **202C** within second multigate device region **204B**. In FIG. **10**, isolation features **260B** fill lower portions of trenches **230A**, **230C**, where one of isolation features **260B** is disposed between lower fin active regions **255L** of fins **208A**, **208B** and one of isolation features **260B** is disposed between lower fin active regions **255L** of fins **208C**, **208D**. Isolation features **260A**, **260B** include different liners-isolation features **260A** include silicon liner **235** disposed on sidewalls of lower fin active regions **255L** and oxide material **250** disposed on silicon liner **235**, while isolation features **260B** includes silicon liner **235** disposed on sidewalls of lower fin active regions **255L**, a dielectric liner (e.g., dielectric liner **240A** or dielectric liner **240B**) disposed on silicon liner **235**, and oxide material **250** disposed on the dielectric liner. In isolation features **260A**, **260B**, oxide material **250** may be referred to as oxide layer **250**. Oxide material **250** can also be referred to as a bulk dielectric and/or bulk dielectric layer of isolation features **260A**, **260B**. Various dimensions and/or characteristics of isolation features **260A**, **260B** can be configured during the processing associated with FIGS. **3-10** to achieve shallow trench isolation (STI) structures, deep trench isolation (DTI) structures, local oxidation of silicon (LOCOS) structures, other suitable isolation structures, or combinations thereof. In the depicted embodiment, isolation features **260A** and isolation features **260B** are STIs.

(27) The etching process is configured to selectively remove dielectric liners **240A**, **240B** with respect to silicon germanium sacrificial layer **258** and oxide material **250**. In other words, the etching process substantially removes dielectric liners **240A**, **240B** but does not remove, or does not substantially remove, silicon germanium sacrificial layer **258** and oxide material **250**. For example, an etchant is selected for the etch process that etches silicon nitride (i.e., dielectric liners **240A**, **240B**) at a higher rate than silicon germanium (i.e., silicon germanium sacrificial layer **258**) and silicon oxide (i.e., oxide material **250**) (i.e., the etchant has a high etch selectivity with respect to silicon nitride). The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, a dry etching process uses an etch gas that includes CHF₃ and/or O₂ to selective etch silicon nitride (i.e., dielectric liners **240A**, **240B**) with respect to silicon germanium (i.e., silicon germanium sacrificial layer **258**) and silicon oxide (i.e., oxide material **250**). In some embodiments, the etch process includes multiple steps.

(28) Turning to FIG. **11**, upper portions of trenches **230A-230C** are filled with dielectric features **270**, each of which includes a dielectric liner **272** and an oxide layer **274** disposed over dielectric liner **272**. In the depicted embodiment, dielectric liner **272** includes a dielectric material having a dielectric constant that is less than about 8.0 ($k < 8.0$). For purposes of the present disclosure, such dielectric materials are referred to as low-k dielectric materials, and dielectric liner **272** can be referred to as a low-k dielectric liner. In some embodiments, dielectric liner **272** includes a

dielectric material having a dielectric constant of about 1.0 to about 8.0. In some embodiments, dielectric liner **272** includes a nitrogen-comprising dielectric material, such as a dielectric material that includes nitrogen in combination with silicon, carbon, and/or oxygen. In such embodiments, dielectric liner **272** can also be referred to as a nitride liner. For example, dielectric liner **272** includes silicon nitride, silicon carbon nitride, silicon oxycarbonitride, or combinations thereof. In some embodiments, dielectric liner **272** includes n-type dopants and/or p-type dopants. For example, dielectric liner **272** can be a boron-doped nitride liner. In some embodiments, dielectric liner **272** includes a dielectric material having a dielectric constant that is less than a dielectric constant of silicon dioxide (SiO_2) ($k \approx 3.9$), such as fluorine-doped silicon oxide (often referred to as fluorosilicate glass (FSG)), carbon-doped silicon oxide (often referred to as carbon-doped FSG), Black Diamond® (Applied Materials of Santa Clara, California), xerogel, aerogel, amorphous fluorinated carbon, parylene, benzocyclobutene (BCB)-based dielectric material, SiLK (Dow Chemical, Midland, Michigan), polyimide, other low-k dielectric material, or combinations thereof. In some embodiments, dielectric liner **272** includes boron silicate glass (BSG), phosphosilicate glass (PSG), and/or boron-doped phosphosilicate glass (BPSG). In some embodiments, oxide layer **274** is similar to oxide material **250** and thus may be formed and include materials as described above with reference to oxide material **250**. For example, oxide layer **274** includes silicon and oxygen, and thus can be referred to as a silicon oxide layer.

(29) In some embodiments, dielectric features **270** are formed by depositing a dielectric layer over multigate device **200**, where the dielectric layer partially fills upper portions of trenches **230A-230C**; depositing an oxide material over the dielectric layer, where the oxide material fills a remainder of upper portions of trenches **230A-230C**; and performing a planarization process, such as a chemical mechanical polishing (CMP) process, to remove any of the oxide material and/or the dielectric layer that is disposed over top surfaces of fins **208-208D**. For example, patterning layer **225** functions as a planarization (e.g., CMP) stop layer, such that the planarization process is performed until reaching and exposing patterning layer **225** of fins **208A-208D**. A remainder of the oxide material and the dielectric layer form each dielectric liner **272** and each oxide layer **274** of dielectric features **270**. In such embodiments, the planarization process removes portions of silicon germanium sacrificial layer **258** disposed over top surfaces of fins **208A-208D**, thereby forming silicon germanium sacrificial features **258'**. In some embodiments, an ALD process is performed to deposit the dielectric layer, such that dielectric liner **272** has a thickness t_6 over multigate device **200**. In some embodiments, an LPCVD process is performed to deposit the dielectric layer, such that dielectric liner **272** has thickness t_6 over multigate device **200**. In some embodiments, thickness t_6 is substantially uniform over various surfaces of multigate device **200**. For example, thickness t_6 along sidewalls of upper portions of trenches **230A-230C** (i.e., over sidewalls of fins **208A-208D** and top and sidewall surfaces of silicon germanium sacrificial layer **258**) is substantially the same as thickness t_6 along bottoms of upper portions of trenches **230A-230C** (i.e., over top surfaces of isolation features **260A, 260B**). In some embodiments, thickness t_6 is about 3 nm to about 10 nm. In some embodiments, dielectric liner **272** is formed by CVD, PVD, HDPCVD, MOCVD, RPCVD, PECVD, APCVD, SAVCD, other suitable deposition processes, or combinations thereof. In some embodiments, the oxide material is deposited over the dielectric layer by FCVD, HPCVD, HARP, CVD, and/or other suitable deposition process. In FIG. **11**, dielectric features **270** fill an entirety of upper portion of trench **230A** and an entirety of upper portion of trench **230C**, whereas in trench **230B**, silicon germanium sacrificial features **258'** partially fill upper portion of trench **230B** and one of dielectric features **270** fills a remainder of upper portion of trench **230B**. Accordingly, a thickness t_7 of oxide layer **274** in upper portion of trench **230B** is less than a thickness t_8 of oxide layer **274** in upper portions of trenches **230A, 230C**. In some embodiments, thickness t_7 is at least about 4 nm, and thickness t_8 is about 4 nm to about 20 nm. In trench **230A**, dielectric liner **272** covers sidewalls of upper fin active regions **255A** of fin **208A** and fin **208B** (which define sidewalls of upper portion of trench **230A**) and a top

surface of isolation feature **260B** filling bottom portion of trench **230A** (which defines a bottom of upper portion of trench **230A**). In trench **230B**, dielectric liner **272** covers sidewalls of silicon germanium sacrificial features **258'** (disposed in upper portion of trench **230B**) and a top surface of isolation feature **260A** filling bottom portion of trench **230B** (which defines a bottom of upper portion of trench **230B**). In trench **230C**, dielectric liner **272** covers sidewalls of upper fin active regions **255A** of fin **208C** and fin **208D** (which define sidewalls of upper portion of trench **230C**) and a top surface of isolation feature **260B** filling bottom portion of trench **230C** (which defines a bottom of upper portion of trench **230C**).

(30) Turning to FIG. **12**, dielectric features **270** are partially removed from trenches **230A-230C**. For example, dielectric features **270** are recessed to expose sidewalls of patterning layer **225** and portions of silicon germanium sacrificial features **258'** disposed along sidewalls of patterning layer **225**. After recessing, dielectric features **270** partially fill upper portions of trenches **230A-230C** (i.e., fills a lower portion of upper portions of trenches **230A-230C**). In some embodiments, an etching process recesses dielectric features **270** until reaching semiconductor layer stacks **210** of fins **208A-208D**. For example, top surfaces of semiconductor layer stacks **210** (here, top surfaces of topmost semiconductor layers **220** of semiconductor layer stacks **210**) are substantially planar with top surfaces of dielectric features **270** after the etching process. In some embodiments, sidewalls of semiconductor layer stacks **210** are partially exposed by the etching process, such that top surfaces of dielectric features **270** are lower than top surfaces of semiconductor layer stacks **210** relative to the top surface of substrate **206** after the etching process. The etching process is configured to selectively remove dielectric liner **272** and oxide layer **274** with respect to silicon germanium sacrificial features **258'** and patterning layer **225**. In other words, the etching process substantially removes dielectric liner **272** and oxide layer **274** but does not remove, or does not substantially remove, silicon germanium sacrificial features **258'** and patterning layer **225**. In some embodiments, the etch process includes multiple steps, for example, implementing a first etchant to recess oxide layer **274** and a second etchant to recess dielectric liner **272**. For example, a first etch step removes oxide layer **274** with high etch selectivity relative to dielectric liner **272** and/or patterning layer **225**, and a second etch step removes dielectric liner **272** with high etch selectivity relative to semiconductor layer stacks **210**, silicon germanium features **258'**, and/or patterning layer **225**. In some embodiments, a first etchant of the first etch step can etch silicon oxide (i.e., oxide layer **274**) at a higher rate than silicon carbon nitride (i.e., dielectric liner **272**) and/or silicon nitride (i.e., patterning layer **225**) (i.e., the etchant has a high etch selectivity with respect to silicon oxide). In some embodiments, a second etchant of the second etch step can etch silicon carbon nitride (i.e., dielectric liner **272**) at a higher rate than silicon germanium (i.e., silicon germanium sacrificial features **258'** and/or semiconductor layers stacks **210**), silicon (i.e., semiconductor layer stacks **210**), and/or silicon nitride (i.e., patterning layer **225**) (i.e., the etchant has a high etch selectivity with respect to silicon carbon nitride). The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, a dry etching process uses an etch gas that includes NF_3 , O_2 and H_2 to achieve selective etching of dielectric liner **272** (including, for example, SiCN , SiOCN , and/or SiOC) with respect to silicon germanium sacrificial features **258'** and patterning layer **225** (including, for example, SiN). In some embodiments, the etching process uses a patterned mask layer as an etch mask, where the patterned mask layer covers silicon germanium sacrificial features **258'** and patterning layer **225** but has openings therein that expose dielectric liner **272** and oxide layer **274**.

(31) Turning to FIG. **13**, dielectric layers **276** are formed over dielectric features **270** to fill a remainder of upper portions of trenches **230A-230C**, thereby forming dielectric fins **280A** over isolation features **260A** and dielectric fins **280B** over isolation features **260B**. Each of dielectric fins **280A**, **280B** includes a respective dielectric layer **276** disposed over a respective dielectric feature **270**. In the depicted embodiment, because some of the trenches (e.g., trench **230B**) are partially filled with silicon germanium sacrificial features **258'**, sidewalls of fins **208A-208D**

physically, directly contact dielectric fins **280B**, but do not physically, directly contact dielectric fins **280A**. For example, each of fins **208A-208D** has a first sidewall that physically contacts a respective dielectric fin **280B** and a second sidewall that is separated from a respective dielectric fin **280A** by a respective silicon germanium sacrificial feature **258'**, such that the second sidewall does not physically contact the respective dielectric fin **280A**. Further, because some of the trenches (e.g., trench **230B**) are partially filled with silicon germanium sacrificial features **258'**, a width of dielectric fins **280A** along the x-direction is less than a width of isolation features **260A** along the x-direction, whereas a width of dielectric fins **280B** along the x-direction is substantially the same as a width of isolation features **260B** along the x-direction. In some embodiments, dielectric layers **276** are formed by depositing a dielectric material over multigate device **200**, where the dielectric material fills remaining upper portions of trenches **230A-230C**, and performing a planarization process, such as a CMP process, to remove any of the dielectric material that is disposed over top surfaces of fins **208A-208D**. For example, patterning layer **225** can function as a planarization stop layer, such that the planarization process is performed until reaching and exposing patterning layer **225** of fins **208A-208D**. A remainder of the dielectric material forms dielectric layers **276**. In some embodiments, the dielectric material is formed by ALD, CVD, PVD, HDPCVD, MOCVD, RPCVD, PECVD, APCVD, SAVCD, other suitable deposition processes, or combinations thereof. Dielectric layers **276** include a dielectric material having a dielectric constant that is greater than a dielectric constant of the dielectric material of dielectric liners **272**. For example, dielectric layers **276** include a dielectric material having a dielectric constant that is greater than or equal to about 8.0 ($k \geq 8.0$). For purposes of the present disclosure, such dielectric materials are referred to as high-k dielectric materials, and dielectric layers **276** can be referred to as a high-k dielectric layers. In some embodiments, dielectric layers **276** includes a dielectric material having a dielectric constant of about 8.0 to about 30.0. In some embodiments, dielectric layers **276** include a metal-and-oxygen-comprising dielectric material having, for example, a dielectric constant of about 9.0 to about 30.0. In such embodiments, the metal can be hafnium, aluminum, and/or zirconium. In such embodiments, dielectric layers **276** can also be referred to as metal oxide layers. For example, dielectric layers **276** include hafnium oxide (e.g., HfO.sub.x), aluminum oxide (AlO.sub.x), zirconium oxide (ZrO.sub.x), or combinations thereof, where x is a number of oxygen atoms in the dielectric material of dielectric layers **276**. In some embodiments, dielectric layers **276** include n-type dopants and/or p-type dopants. In some embodiments, dielectric layers **276** include HfO.sub.2 , HfSiO , HfSiO.sub.4 , HfSiON , HfLaO , HfTaO , HfTiO , HfZrO , HfAlO.sub.x , ZrO , ZrO.sub.2 , ZrSiO.sub.2 , AlO , AlSiO , Al.sub.2O.sub.3 , TiO , TiO.sub.2 , LaO , LaSiO , Ta.sub.2O.sub.3 , Ta.sub.2O.sub.5 , Y.sub.2O.sub.3 , SrTiO.sub.3 , BaZrO , BaTiO.sub.3 , $(\text{Ba,Sr})\text{TiO.sub.3}$, $\text{HfO.sub.2—Al.sub.2O.sub.3}$, other suitable high-k dielectric material, or combinations thereof.

(32) Turning to FIG. **14**, an etching process is performed to remove patterning layer **225** from fins **208A-208D** and portions of silicon germanium sacrificial features **258'** disposed along sidewalls of patterning layer **225**, thereby forming openings **284** (defined between dielectric layers **286**) that expose semiconductor layer stacks **210** of fins **208A-208D**. The etching process is configured to selectively remove patterning layer **225** and silicon germanium sacrificial features **258'** with respect to dielectric layers **276** and semiconductor layers **220** of semiconductor layer stacks **210**. In other words, the etching process substantially removes patterning layer **225** and silicon germanium sacrificial features **258'** (in particular, portions of silicon germanium sacrificial features **258'** disposed along sidewalls of patterning layer **225**) but does not remove, or does not substantially remove, dielectric layers **276** and semiconductor layers **220**. In some embodiments, the etch process includes multiple steps, for example, implementing a first etchant to remove silicon germanium sacrificial features **258'** and a second etchant to remove patterning layer **225**. For example, a first etch step removes silicon germanium sacrificial features **258'** with high etch selectivity relative to dielectric layers **276** and/or patterning layer **225**, and a second etch step

removes patterning layer **225** with high etch selectivity relative to dielectric layers **276** and/or silicon germanium features **258'**. In some embodiments, a first etchant of the first etch step can etch silicon germanium (i.e., silicon germanium sacrificial features **258'**) at a higher rate than high-k dielectric material (i.e., dielectric layers **276**) and/or silicon nitride (i.e., patterning layer **225**) (i.e., the etchant has a high etch selectivity with respect to silicon germanium). In some embodiments, a second etchant of the second etch step can etch silicon nitride (i.e., patterning layer **225**) at a higher rate than high-k dielectric material (i.e., dielectric layers **276**), silicon germanium (i.e., silicon germanium sacrificial features **258'** and/or semiconductor layers stacks **210**), and silicon (i.e., semiconductor layer stacks **210**) (i.e., the etchant has a high etch selectivity with respect to silicon nitride). The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, the first etchant is a wet etchant that includes NH_4OH , H_2O_2 , and H_2O , a wet etchant that includes O_3 and DHF, a dry etch gas that includes F_2 and NH_3 , or combinations thereof. In some embodiments, the second etchant is a wet etchant that includes H_3PO_4 . In some embodiments, the etching process uses a patterned mask layer as an etch mask, where the patterned mask layer covers dielectric layers **276** but has openings therein that expose patterning layer **225** and, in some embodiments, portions of silicon germanium sacrificial features **258'** disposed along sidewalls of patterning layer **225**.

(33) Turning to FIG. **15**, dummy gate stacks **290** are formed over portions of fins **208A-208D**, dielectric fins **280A**, and dielectric fins **280B**. Dummy gate stacks **290** fill portions of openings **284**. Dummy gate stacks **290** extend lengthwise in a direction that is different than (e.g., orthogonal to) the lengthwise direction of fins **208A-208D**. For example, dummy gate stacks **290** extend substantially parallel to one another along the x-direction, having a length defined in the x-direction, a width defined in the y-direction, and a height defined in the z-direction. Dummy gate stacks **290** are disposed over channel regions (C) of multigate device **200** and between source/drain regions (S/D) of multigate device **200**, which are exposed by a remainder of openings **284** in dielectric layers **286**. In the X-Z plane, dummy gate stacks **290** are disposed on top surfaces of fins **208A-208D** (in particular, top surfaces of semiconductor layer stacks **210**), top surfaces of dielectric layers **276** of dielectric fins **280A**, **280B**, and sidewall surfaces of dielectric layers **276** of dielectric fins **280A**, **280B**, such that dummy gate stacks **290** wrap portions of dielectric layers **276** of dielectric fins **280A**, **280B**. In the Y-Z plane, dummy gate stacks **290** are disposed over top surfaces of respective channel regions of fins **208A-208D**, such that dummy gate stacks **290** interpose respective source/drain regions of fins **208A-208D**. Each dummy gate stack **290** includes a dummy gate dielectric **292**, a dummy gate electrode **294**, and a hard mask **296** (including, for example, a first mask layer **297** and a second mask layer **298**). Dummy gate dielectric **292** includes a dielectric material, such as silicon oxide, a high-k dielectric material, other suitable dielectric material, or combinations thereof. In some embodiments, dummy gate dielectric **292** includes an interfacial layer (including, for example, silicon oxide) and a high-k dielectric layer disposed over the interfacial layer. Dummy gate electrode **294** includes a suitable dummy gate material, such as polysilicon. In some embodiments, dummy gate stacks **290** include numerous other layers, for example, capping layers, interface layers, diffusion layers, barrier layers, or combinations thereof. Dummy gate stacks **290** are formed by deposition processes, lithography processes, etching processes, other suitable processes, or combinations thereof. For example, a first deposition process is performed to form a dummy gate dielectric layer over multigate device **200**, a second deposition process is performed to form a dummy gate electrode layer over the dummy gate dielectric layer, and a third deposition process is performed to form a hard mask layer over the dummy gate electrode layer. The deposition processes include CVD, PVD, ALD, HDPCVD, MOCVD, RPCVD, PECVD, LPCVD, ALCVD, APCVD, plating, other suitable methods, or combinations thereof. A lithography patterning and etching process is then performed to pattern the hard mask layer, the dummy gate electrode layer, and the dummy gate dielectric layer to form dummy gate stacks **290**, which include dummy gate dielectric **292**, dummy gate electrode **294**, and hard mask **296** as

depicted in FIG. 15. The lithography patterning processes include resist coating (for example, spin-on coating), soft baking, mask aligning, exposure, post-exposure baking, developing the resist, rinsing, drying (for example, hard baking), other suitable lithography processes, or combinations thereof. The etching processes include dry etching processes, wet etching processes, other etching methods, or combinations thereof.

(34) Turning to FIG. 16, gate spacers 299 are formed along sidewalls of dummy gate stacks 290, thereby forming gate structures 300 (which collectively refers to dummy gate stacks 290 and gate spacers 299). In FIG. 16, portions of fins 208A-208D in source/drain regions of multigate device 200 (i.e., source/drain regions of fins 208A-208D that are not covered by gate structures 300) are also at least partially removed to form source/drain recesses (trenches) 310. Processing associated with forming gate spacers 299 and/or source/drain recesses 310 reduces a thickness of exposed portions of dielectric layers 276 (e.g., portions of dielectric layers 276 in source/drain regions of multigate device 200) relative to unexposed portions of dielectric layers 276 (e.g., portions of dielectric layers 276 in channel regions of multigate device 200). For example, dielectric layers 276 have a thickness t_9 , and etching processes implemented to form gate spacers 299 and/or source/drain recesses 310 reduce, intentionally or unintentionally, a thickness of exposed portions of dielectric layers 276 from thickness 19 to thickness t_{10} . In some embodiments, thickness 19 is about 10 nm to about 40 nm, and thickness t_{10} is less than about 30 nm. In some embodiments, a difference (offset) of thickness 19 to thickness t_{10} is about 5 nm to about 20 nm. Accordingly, portions of dielectric layers 276 disposed in channel regions of multigate device 200 under gate structures 300 (here, dummy gate stacks 290 and gate spacers 299) have thickness t_9 while portions of dielectric layers 276 disposed in source/drain regions of multigate device 200 and not disposed under gate structures 300 have thickness t_{10} . In some embodiments, exposed portions of dielectric layers 276 are completely removed when forming gate spacers 299 and/or source/drain recesses 310 (i.e., thickness $t_{10}=0$).

(35) Gate spacers 299 are disposed adjacent to (i.e., along sidewalls of) respective dummy gate stacks 290. Gate spacers 299 are formed by any suitable process and include a dielectric material. The dielectric material can include silicon, oxygen, carbon, nitrogen, other suitable material, or combinations thereof (e.g., silicon oxide, silicon nitride, silicon oxynitride, silicon carbide, silicon carbon nitride, silicon oxycarbide, and/or silicon oxycarbonnitride). For example, a dielectric layer including silicon and nitrogen, such as a silicon nitride layer, is deposited over multigate device 200 and etched (e.g., anisotropically etched) to form gate spacers 299. In some embodiments, gate spacers 299 include a multi-layer structure, such as a first dielectric layer that includes silicon nitride and a second dielectric layer that includes silicon oxide. In some embodiments, more than one set of spacers, such as seal spacers, offset spacers, sacrificial spacers, dummy spacers, and/or main spacers, are formed adjacent to dummy gate stacks 290. In such embodiments, the various sets of spacers can include materials having different etch rates. For example, a first dielectric layer including silicon and oxygen (e.g., silicon oxide) is deposited and etched to form a first spacer set adjacent to sidewalls of dummy gate stacks 290, and a second dielectric layer including silicon and nitrogen (e.g., silicon nitride) is deposited and etched to form a second spacer set adjacent to the first spacer set.

(36) In the depicted embodiment, an etching process completely removes semiconductor layer stacks 210 in source/drain regions of multigate device 200, thereby exposing fin portions 206' in source/drain regions of multigate device 200. The etching process also completely removes portions of silicon germanium sacrificial features 258' that are disposed along sidewalls of semiconductor layer stacks 210 in source/drain regions of multigate device 200. In the depicted embodiment, each source/drain recess 310 thus has a sidewall defined by a respective one of dielectric fins 280A, a sidewall defined by a respective one of dielectric fins 280B, and sidewalls defined by both remaining portions of semiconductor layer stacks 210 in channel regions of multigate device 200 and remaining portions of silicon germanium sacrificial features 258'

disposed along sidewalls of the remaining portions of semiconductor layer stacks **210** (which remaining portions are disposed under gate structures **300**). Each source/drain recess **310** further has a bottom defined by a respective fin portion **206'** and respective isolation feature **260A**. In some embodiments, the etching process removes some, but not all, of semiconductor layer stacks **210**, such that source/drain recesses **310** have bottoms defined by respective semiconductor layers **215** or semiconductor layer **220**. In some embodiments, the etching process further removes some, but not all, of fin portions **206'** of fins **208A-208D**, such that source/drain recesses **310** extend below top surfaces of isolation features **260A**, **260B**. The etching process can include a dry etching process, a wet etching process, other suitable etching process, or combinations thereof. In some embodiments, the etching process is a multi-step etch process. For example, the etching process may alternate etchants to separately and alternately remove semiconductor layers **215** and semiconductor layers **220**. In some embodiments, parameters of the etching process are configured to selectively etch semiconductor layer stacks **210** with minimal (to no) etching of gate structures **300** (i.e., dummy gate stacks **290** and gate spacers **299**), dielectric fins **280A**, **280B**, and/or isolation features **260A**, **260B**. In some embodiments, a lithography process, such as those described herein, is performed to form a patterned mask layer that covers gate structures **300** and/or dielectric fins **280A**, **280B**, and the etching process uses the patterned mask layer as an etch mask. In such embodiments, thicknesses of dielectric layers **276** are not reduced in the source/drain regions.

(37) Turning to FIG. **17** and FIG. **18**, inner spacers **315A** and inner spacers **315B** are formed under gate structures **300** (in particular, under gate spacers **299**) along sidewalls of semiconductor layers **215** in channel regions of multigate device **200**. Inner spacers **315A** separate semiconductor layers **220** from one another and bottommost semiconductor layers **220** from fin portions **206'**, while inner spacers **315B** separate semiconductor layers **220** and inner spacers **315A** from dielectric fins **280A**. In FIG. **17**, a first etching process is performed that selectively etches semiconductor layers **215** exposed by source/drain trenches **310** with minimal (to no) etching of semiconductor layers **220**, fin portions **206'**, isolation features **260A**, dielectric fins **280A**, dielectric fins **280B**, and gate structures **300**, such that gaps **315A'** are formed between semiconductor layers **220** and between fin portions **206'** and semiconductor layers **220**. The first etching process further selectively etches silicon germanium sacrificial features **258'** that are exposed by source/drain trenches **310**, such that gaps **315B'** are formed between semiconductor layers **220** and dielectric fins **280A** and between gaps **315A'** and dielectric fins **280A**. Gaps **315A'** and gaps **315B'** are disposed under gate spacers **299**. Semiconductor layers **220** are thus suspended under gate spacers **299**, separated from one another by gaps **315A'** and separated from dielectric fins **280A** by gaps **315B'**. In some embodiments, gaps **315A'** and/or gaps **315B'** extend at least partially under dummy gate stacks **290**. The first etching process is configured to laterally etch (e.g., along the y-direction) semiconductor layers **215**, thereby reducing a length of semiconductor layers **215** along the y-direction. The first etching process is a dry etching process, a wet etching process, other suitable etching process, or combinations thereof. In FIG. **18**, a deposition process then forms a spacer layer over gate structures **300** and over features defining source/drain recesses **310** (e.g., semiconductor layers **215**, semiconductor layers **220**, fin portions **206'**, dielectric fins **280A**, dielectric fins **280B**, and isolation features **260A**), such as CVD, PVD, ALD, HDPCVD, MOCVD, RPCVD, PECVD, LPCVD, ALCVD, APCVD, plating, other suitable methods, or combinations thereof. The spacer layer partially (and, in some embodiments, completely) fills source/drain recesses **310**. The deposition process is configured to ensure that the spacer layer fills gaps **315A'** and gaps **315B'**. A second etching process is then performed that selectively etches the spacer layer to form inner spacers **315A**, which fill gaps **315A'**, and inner spacers **315B**, which fill gaps **315B'**, as depicted in FIG. **18** with minimal (to no) etching of semiconductor layers **220**, fin portions **206'**, isolation features **260A**, dielectric fins **280A**, dielectric fins **280B**, and gate structures **300**. The spacer layer (and thus inner spacers **315A** and inner spacers **315B**) includes a material that is different than a material of

semiconductor layers **220**, a material of fin portions **206'**, a material of isolation features **260A**, a material of dielectric fins **280A**, a material of dielectric fins **280B**, a material of dummy gate stacks **290**, and/or a material of gate spacers **299** to achieve desired etching selectivity during the second etching process. In some embodiments, the spacer layer includes a dielectric material that includes silicon, oxygen, carbon, nitrogen, other suitable material, or combinations thereof (for example, silicon oxide, silicon nitride, silicon oxynitride, silicon carbide, and/or silicon oxycarbonitride). In some embodiments, the spacer layer includes a low-k dielectric material, such as those described herein. In some embodiments, dopants (for example, p-type dopants, n-type dopants, or combinations thereof) are introduced into the dielectric material, such that the spacer layer includes a doped dielectric material.

(38) Turning to FIG. **19**, epitaxial source/drain features are formed in source/drain recesses **310**. For example, a semiconductor material is epitaxially grown from fin portions **206'** of substrate **206** and semiconductor layers **220** exposed by source/drain recesses **310**, forming epitaxial source/drain features **320A** in source/drain recesses **310** that correspond with n-type transistors (e.g., source/drain regions in n-type transistor regions **202A**, **202C**) and epitaxial source/drain features **320B** in source/drain recesses **310** that correspond with p-type transistors (e.g., source/drain regions in p-type transistor region **202B**). As described in detail below, epitaxial source/drain features **320A**, **320B** have asymmetric profiles along the X-Z plane, which result from epitaxial growth differences (variations) along the x-direction that arise from positions of sidewalls of fin portions **206'** and sidewalls of semiconductor layers **220** relative to dielectric fins **280A**, **280B**. In some embodiments, such as depicted, epitaxial source/drain features **320A**, **320B** do not completely fill source/drain recesses **310**, such that top surfaces of epitaxial source/drain features **320A**, **320B** are lower than top surfaces of dielectric layers **276** relative to the top surface of substrate **206**. In some embodiments, epitaxial source/drain features **320A**, **320B** completely fill source/drain recesses **310**, such that top surfaces of epitaxial source/drain features **320A**, **320B** are substantially planar with top surfaces of dielectric layers **276** or higher than top surfaces of dielectric layers **276** relative to the top surface of substrate **206**. An epitaxy process can use CVD deposition techniques (for example, LPCVD, VPE, and/or UHV-CVD), molecular beam epitaxy, other suitable epitaxial growth processes, or combinations thereof. The epitaxy process can use gaseous and/or liquid precursors, which interact with the composition of fin portions **206'** and/or semiconductor layers **220**. Epitaxial source/drain features **320A**, **320B** are doped with n-type dopants and/or p-type dopants. In some embodiments, for the n-type transistors, epitaxial source/drain features **320A** include silicon, which can be doped with carbon, phosphorous, arsenic, other n-type dopant, or combinations thereof (for example, forming Si:C epitaxial source/drain features, Si:P epitaxial source/drain features, or Si:C:P epitaxial source/drain features). In some embodiments, for the p-type transistors, epitaxial source/drain features **320B** include silicon germanium or germanium, which can be doped with boron, other p-type dopant, or combinations thereof (for example, forming Si:Ge:B epitaxial source/drain features). In some embodiments, epitaxial source/drain features **320A** and/or epitaxial source/drain features **320B** include more than one epitaxial semiconductor layer, where the epitaxial semiconductor layers can include the same or different materials and/or dopant concentrations. In some embodiments, epitaxial source/drain features **320A**, **320B** include materials and/or dopants that achieve desired tensile stress and/or compressive stress in respective channel regions of the n-type transistors and/or the p-type transistors. In some embodiments, epitaxial source/drain features **320A**, **320B** are doped during deposition by adding impurities to a source material of the epitaxy process (i.e., in-situ). In some embodiments, epitaxial source/drain features **320A**, **320B** are doped by an ion implantation process subsequent to a deposition process. In some embodiments, annealing processes (e.g., rapid thermal annealing and/or laser annealing) are performed to activate dopants in epitaxial source/drain features **320A**, **320B** and/or other source/drain regions (for example, heavily doped source/drain regions and/or lightly doped source/drain (LDD) regions). In some embodiments, epitaxial

source/drain features **320A**, **320B** are formed in separate processing sequences that include, for example, masking p-type transistor region **202B** when forming epitaxial source/drain features **320A** in n-type transistor regions **202A**, **202C** and masking n-type transistor regions **202A**, **202C** when forming epitaxial source/drain features **320B** in p-type transistor region **202B**.

(39) Turning to FIG. **20**, a deposition process (such as CVD, PVD, ALD, HDPCVD, MOCVD, RPCVD, PECVD, LPCVD, ALCVD, APCVD, other suitable methods, or combinations thereof) is performed to form an inter-level dielectric (ILD) layer **330** over multigate device **200** and a CMP process and/or other planarization process is performed until reaching (exposing) top portions (or top surfaces) of dummy gate stacks **290**. In some embodiments, ILD layer **330** is formed by FCVD, HARP, HDP, or combinations thereof. In some embodiments, such as depicted, the planarization process removes hard mask layers **296** of dummy gate stacks **290** to expose underlying dummy gate electrodes **294** of dummy gate stacks **290**, such as polysilicon gate electrodes. ILD layer **330** is disposed over epitaxial source/drain features **320A**, **320B**, dielectric fins **280A**, and dielectric fins **280B** in source/drain regions of multigate device **200**. ILD layer **330** is further disposed between adjacent gate structures **300**. ILD layer **330** includes a dielectric material including, for example, silicon oxide, carbon doped silicon oxide, silicon nitride, silicon oxynitride, TEOS-formed oxide, PSG, BSG, BPSG, FSG, Black Diamond® (Applied Materials of Santa Clara, California), xerogel, aerogel, amorphous fluorinated carbon, parylene, BCB-based dielectric material, SiLK (Dow Chemical, Midland, Michigan), polyimide, other suitable dielectric material, or combinations thereof. In some embodiments, ILD layer **330** includes a dielectric material having a dielectric constant that is less than a dielectric constant of silicon dioxide (e.g., $k < 3.9$). In some embodiments, ILD layer **330** includes a dielectric material having a dielectric constant that is less than about 2.5 (i.e., an extreme low-k (ELK) dielectric material), such as silicon dioxide (SiO₂) (for example, porous silicon dioxide), silicon carbide (SiC), and/or carbon-doped oxide (for example, a SiCOH-based material (having, for example, Si—CH₃ bonds)), each of which is tuned/configured to exhibit a dielectric constant less than about 2.5. ILD layer **330** can include a multilayer structure having multiple dielectric materials. In some embodiments, such as depicted, a contact etch stop layer (CESL) **332** is disposed between ILD layer **330** and epitaxial source/drain features **320A**, **320B**, dielectric layers **276** (of dielectric fins **280A**, **280B**), and gate spacers **299**. CESL **332** includes a material different than ILD layer **330**, such as a dielectric material that is different than the dielectric material of ILD layer **330**. For example, where ILD layer **330** includes a dielectric material that includes silicon and oxygen and having a dielectric constant that is less than about the dielectric constant of silicon dioxide, CESL **332** can include silicon and nitrogen, such as silicon nitride or silicon oxynitride. ILD layer **330** and CESL **332** can be a portion of a multilayer interconnect (MLI) feature **340** of multigate device **200**. MLI feature **340** electrically couples various devices (for example, p-type transistors and/or n-type transistors of multigate device **200**, resistors, capacitors, and/or inductors) and/or components (for example, gate electrodes and/or epitaxial source/drain features of p-type transistors and/or n-type transistors), such that the various devices and/or components can operate as specified by design requirements of multigate device **200**. MLI feature **340** includes a combination of dielectric layers and electrically conductive layers (e.g., metal layers) configured to form various interconnect structures. The conductive layers are configured to form vertical interconnect features, such as device-level contacts and/or vias, and/or horizontal interconnect features, such as conductive lines. Vertical interconnect features typically connect horizontal interconnect features in different layers (or different planes) of MLI feature **340**. During operation, the interconnect features are configured to route signals between the devices and/or the components of multigate device **200** and/or distribute signals (for example, clock signals, voltage signals, and/or ground signals) to the devices and/or the components of multigate device **200**.

(40) Turning to FIGS. **21-26**, a gate replacement process is performed to replace dummy gate stacks **290** with metal gate stacks and a channel release process is performed to form suspended

channel layers in channel regions of multigate device **200**, where the metal gate stacks at least partially surround the suspended channel layers. For case of description and understanding, FIGS. **21-26** are taken (cut) through one of gate structures **300** along line G-G' in FIG. **20** (and are thus referred to as metal gate cut perspective views). Turning to FIG. **21**, gate openings **350** are formed in gate structures **300** by partially removing dummy gate stacks **290**. For example, an etching process is performed that recesses dummy gate electrodes **294** until dielectric layers **276** of dummy fins **280A**, **280B** are exposed and extend (protrude) from between remaining portions of dummy gate electrodes **294**. In FIG. **21**, after recessing dummy gate electrodes **294**, topmost surfaces of dummy gate electrodes **294** are lower than topmost surfaces of dielectric layers **276** of dummy fins **280A**, **280B** relative to top surface of substrate **206**. In some embodiments, a height difference Δh_1 between topmost surfaces of dummy gate electrodes **294** and topmost surfaces of dielectric layers **276** in channel regions of multigate device **200** is about 5 nm to about 30 nm. The etching process is configured to selectively remove dummy gate electrodes **294** with respect to ILD layer **330**, CESL **332**, gate spacers **299**, and/or dummy gate dielectrics **292**. In other words, the etching process substantially removes dummy gate electrodes **294** but does not remove, or does not substantially remove, ILD layer **330**, CESL **332**, gate spacers **299**, and/or dummy gate dielectrics **292**. For example, an etchant is selected for the etch process that etches polysilicon (i.e., dummy gate electrodes **294**) at a higher rate than silicon oxide and/or silicon nitride (i.e., ILD layer **330**, CESL **332**, gate spacers **299**, and/or dummy gate dielectrics **292**) (i.e., the etchant has a high etch selectivity with respect to polysilicon). In some embodiments, such as depicted, the etching process does not remove dummy gate dielectrics **232**, such that dummy gate dielectrics **292** remain covering exposed portions of dielectric layers **276**. In some embodiments, the etching process partially or completely removes dummy gate dielectrics **292**. The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, a dry etching process uses an etch gas that includes HBr and/or Cl₂ to achieve selective etching of polysilicon (i.e., dummy gate electrodes **294**) with respect to silicon oxide and/or silicon nitride (i.e., ILD layer **330**, gate spacers **299**, and/or dummy gate dielectrics **292**). In some embodiments, the etch process includes multiple steps. In some embodiments, the etching process uses a patterned mask layer as an etch mask, where the patterned mask layer covers ILD layer **330**, CESL **332**, and/or gate spacers **299** but has openings therein that expose dummy gate electrodes **294**.

(41) Turning to FIG. **22** and FIG. **23**, dielectric layers **276** are removed from dielectric fins **280B** in channel regions of multigate device **200**. In FIG. **22**, a lithography process, such as those described herein, is performed to form a patterned mask layer **360**, which includes a mask portion **360A**, a mask portion **360B**, a mask portion **360C**, an opening **362A** defined by mask portions **360A**, **360B**, and an opening **362B** defined by mask portions **360B**, **360C**. In some embodiments, patterned mask layer **360** is a patterned resist layer. Mask portions **360A-360C** cover dielectric fins that span interface regions between different device regions, such as dielectric fins **280A**. For example, mask portion **360A** covers a first device interface region between first multigate device region **204A** and another device region (for example, positioned left of first multigate device region **204A**), mask portion **360B** covers a second device interface region between multigate device region **204A** and multigate device region **204B**, and mask portion **360C** covers a third device interface region between second multigate device region **204B** and another device region (for example, positioned right of second multigate device region **204B**). Dielectric fins **280A** spanning the first device interface region, the second device interface region, and the third device interface region are thus covered by mask portions **360A-360C**. Openings **362A**, **362B** expose dielectric fins that span interface regions between different transistors and/or devices within a device region, such as dielectric fins **280B**. For example, opening **362A** exposes a first transistor interface region between n-type transistor region **202A** and p-type transistor region **202B**, and opening **362B** exposes a second transistor interface region between p-type transistor region **202B** and n-type transistor region **202C**. In furtherance of the depicted embodiment, opening **362A** exposes portions of gate

structures **300** in n-type transistor device region **202A** and p-type transistor region **202B** that are adjacent to the first transistor interface region, and opening **362B** exposes portions of gate structures **300** in p-type transistor device region **202B** and n-type transistor region **202C** that are adjacent to the second transistor interface region. Openings **362A**, **362B** thus expose dielectric fins **280B** spanning the first transistor interface region and the second transistor interface region, portions of dummy gate dielectrics **292**, and portions of dummy gate electrodes **294**.

(42) In FIG. **23**, an etching process is then performed to remove dielectric layers **276** from the portions of dielectric fins **280B** that are disposed in channel regions of multigate device **200**, such that dielectric fins **280B** have first portions **280B-1** in channel regions of multigate device **200** and second portions **280B-2** in source/drain regions of multigate device **200**. First portions **280B-1** include dielectric layer **276** and dielectric feature **270** (i.e., dielectric liner **272** and oxide layer **274**), while second portions **280B-2** include only dielectric feature **270**. In the depicted embodiment, the etching process selectively etches dielectric layers **276** with minimal (to no) etch of gate spacers **299**, ILD layer **330**, and/or CESL **332**. In other words, the etching process substantially removes dielectric layers **276** but does not remove, or does not substantially remove, gate spacers **299**, ILD layer **330**, and/or CESL **332**. For example, an etchant is selected for the etch process that etches metal oxide (i.e., dielectric layers **276**) at a higher rate than silicon oxide and/or silicon nitride (i.e., ILD layer **330**, CESL **332**, and/or gate spacers **299**) (i.e., the etchant has a high etch selectivity with respect to metal oxide). In some embodiments, the etchant has a first etch selectivity between dielectric layers **276** and gate spacers **299**, ILD layer **330**, and/or CESL **332** and a second etch selectivity between dielectric layers **276** and dummy gate dielectrics **292** and/or dummy gate electrodes **294**, where the first etch selectivity is greater than the second etch selectivity. In such embodiments, such as depicted in FIG. **23**, the etching process does not remove, or does not substantially remove, gate spacers **299**, ILD layer **330**, and/or CESL **332**, but partially removes dummy gate dielectrics **292** and/or dummy gate electrodes **294**. For example, the etching process removes portions of dummy gate dielectrics **292** that cover dielectric layers **276** in openings **362A**, **362B** and partially removes portions of dummy gate dielectrics **292** and/or dummy gate electrodes **294** that cover fins **208A-208D** in channel regions of multigate device **200**. In some embodiments, the etching process partially removes patterned mask layer **360**. The etching process is a dry etching process, a wet etching process, or a combination thereof. Thereafter, patterned mask layer **360**, or any remaining portion thereof, is removed from multigate device **200**, for example, by a resist stripping process, an etching process, other suitable process, or combination thereof.

(43) In FIG. **24**, a remainder of dummy gate electrodes **294** is removed from gate openings **350**. For example, an etching process completely removes dummy gate electrodes **294** to expose semiconductor layer stacks **210**. The etching process is similar to the etching process described above with reference to FIG. **21**. The etching process is configured to selectively etch dummy gate electrodes **294** with minimal (to no) etching of other features of multigate device **200**, such as gate spacers **299**, dielectric fins **280A**, dielectric fins **280B**, ILD layer **330**, CESL **332**, and/or semiconductor layers **220**. In the depicted embodiment, the etching process further selectively etches dummy gate electrodes **294** with minimal (to no) etching of dummy gate dielectrics **292**, such that dummy gate dielectrics **292** remain covering semiconductor layers stacks **210** and dielectric layers **276** of dielectric fins **270** in channel regions of multigate device **200**. In some embodiments, the etching process is configured to completely or partially remove dummy gate dielectrics **292**. The etching process is a dry etching process, a wet etching process, other suitable etching process, or combinations thereof. In some embodiments, the etching process is a multi-step etch process. For example, the etching process may alternate etchants to separately remove various layers of dummy gate stacks, such as dummy gate electrodes **294**, dummy gate dielectrics **292**, and/or hard mask layers. In some embodiments, a lithography process, such as those described herein, is performed to form a patterned mask layer that covers ILD layer **330** and/or gate spacers

299 during the etching process.

(44) In FIG. **25**, semiconductor layers **215** of semiconductor layer stacks **210** exposed by gate openings **350** are selectively removed from channel regions of multigate device **200**, thereby forming suspended semiconductor layers **220'** separated from one another and/or fin portions **206'** by gaps **365A**. Silicon germanium sacrificial features **258'** are also selectively removed from channel regions of multigate device **200**, thereby forming gaps **365B** between suspended semiconductor layers **220'** and dielectric fins **280A**. As such, n-type transistor region **202A**, p-type transistor region **202B**, and n-type transistor region **202C** each have at least one suspended semiconductor layer **220'**. For example, n-type transistor region **202A**, p-type transistor region **202B**, and n-type transistor region **202C** each include three suspended semiconductor layers **220'** vertically stacked along the z-direction, which will provide three channels through which current can flow between respective epitaxial source/drain features (epitaxial source/drain features **320A** or epitaxial source/drain features **320B**) during operation of the transistors. Suspended semiconductor layers **220'** are thus referred to as channel layers **220'** hereinafter, and the process depicted in FIG. **25** can be referred to as a channel release process. A spacing **s1** is defined between channel layers **220'** along the z-direction, and a spacing **s2** is defined between channel layers **220'** and dielectric fins **280A** along the x-direction. Spacing **s1** and spacing **s2** correspond with widths of gaps **365A** and gaps **365B**, respectively. In some embodiments, spacing **s1** is about equal to a thickness **t1** of semiconductor layers **215**, and spacing **s2** is about equal to thickness **t5** of silicon germanium sacrificial features **258'**, though the present disclosure contemplates embodiments where spacing **s1** is greater than or less than thickness **t1** and spacing **s2** is greater than or less than thickness **t5**. In some embodiments, each channel layer **220'** has nanometer-sized dimensions and can be referred to as “nanostructures,” alone or collectively. For example, each channel layer **220'** can have a width along the x-direction that is about 6 nm to about 80 nm, a length along the y-direction that is about 8 nm to about 150 nm, and a thickness along the z-direction that is about 3 nm to about 15 nm. The present disclosure further contemplates embodiments channel layers **220'** having sub-nanometer dimensions. In some embodiments, channel layers **220'** have cylindrical-shaped profiles (e.g., nanowires), rectangular-shaped profiles (e.g., nanobars), sheet-shaped profiles (e.g., nanosheets (i.e., dimensions in the X-Y plane are greater than dimensions in the X-Z plane and the Y-Z plane to form sheet-like structures), or any other suitable shaped profile.

(45) In some embodiments, an etching process is performed to selectively etch semiconductor layers **215** and silicon germanium sacrificial features **258'** with minimal (to no) etching of semiconductor layers **220**, fin portions **206'**, isolation features **260A**, dielectric fins **280A**, dielectric fins **280B**, gate spacers **299**, inner spacers **315A**, inner spacers **315B**, ILD layer **330**, and/or CESL **332**. In some embodiments, an etchant is selected for the etch process that etches silicon germanium (i.e., semiconductor layers **215** and silicon germanium sacrificial features **258'**) at a higher rate than silicon (i.e., semiconductor layers **220** and fin portions **206'**) and dielectric materials (i.e., isolation features **260A**, dielectric fins **280A**, dielectric fins **280B**, gate spacers **299**, inner spacers **315A**, inner spacers **315B**, ILD layer **330**, and/or CESL **332**) (i.e., the etchant has a high etch selectivity with respect to silicon germanium). In some embodiments, the etching process partially, but minimally, etches semiconductor layers **220**, fin portions **206'**, and/or isolation features **260A**. For example, in FIG. **25**, the etching process slightly recesses fin portions **206'**, such that topmost surfaces of fin portions **206'** in channel regions of multigate device **200** are lower than topmost surfaces of fin portions **206'** in source/drain regions of multigate device **200** relative to a top surface of substrate **206**. In furtherance of the example, in FIG. **25**, the etching process also slightly recesses portions of isolation features **260A** that are exposed by gate openings **350**, such as dielectric liners **235** and portions of oxide material **250** not covered by dielectric fins **280A**. The etching process does not recess portions of oxide material **250** disposed under dielectric fins **280A**, such that isolation features **260A** have oxide extensions **250'** in channel regions of multigate device **200**. In such embodiments, topmost surface of fin portions **206'** in channel regions of multigate

device **200** are lower than topmost surfaces of oxide extensions **250'** of isolation features **260A** relative to the top surface of substrate **206**. In some embodiments, topmost surfaces of recessed portions of isolation features **260** (i.e., dielectric liners **235** and oxide material **250**) are substantially planar with topmost surfaces of fin portions **206'** in channel regions of multigate device **200**.

(46) The etching process is a dry etching process, a wet etching process, or a combination thereof. In some embodiments, a dry etching process (such as an RIE process) utilizes a fluorine-containing gas (for example, SF₆) to selectively etch semiconductor layers **215** and silicon germanium sacrificial features **258'**. In some embodiments, a ratio of the fluorine-containing gas to an oxygen-containing gas (for example, O₂), an etching temperature, and/or an RF power may be tuned to selectively etch silicon germanium or silicon. In some embodiments, a wet etching process utilizes an etching solution that includes NH₄OH and H₂O to selectively etch semiconductor layers **215** and silicon germanium sacrificial features **258'**. In some embodiments, a chemical vapor phase etching process using HCl selectively etches semiconductor layers **215** and silicon germanium sacrificial features **258'**. In some embodiments, before performing the etching process, an oxidation process can be implemented to convert semiconductor layers **215** and silicon germanium sacrificial features **258'** into silicon germanium oxide features, where the etching process then removes the silicon germanium oxide features. In some embodiments, the etch process includes multiple steps. In some embodiments, the etching process uses a patterned mask layer as an etch mask, where the patterned mask layer covers ILD layer **330**, CESL **332**, and/or gate spacers **299** but has openings therein that expose channel regions of multigate device **200**. In some embodiments, after removing semiconductor layers **215** and silicon germanium sacrificial features **258'**, an etching process is performed to modify a profile of channel layers **220'** to achieve desired dimensions and/or desired shapes.

(47) Turning to FIG. **26**, metal gate stacks **380** (also referred to as metal gates and/or high-k/metal gates) are formed in gate openings **350**. Metal gate stacks **380** are configured to achieve desired functionality according to design requirements of multigate device **200**. Metal gate stacks **380** each include a gate dielectric **382** (for example, a gate dielectric layer) and a gate electrode **384** (for example, a work function layer and a bulk conductive layer). Metal gate stacks **380** may include numerous other layers, for example, capping layers, interface layers, diffusion layers, barrier layers, hard mask layers, or combinations thereof. In some embodiments, forming metal gate stacks **380** includes depositing a gate dielectric layer over multigate device **200**, where the gate dielectric layer partially fills gate openings **350**, depositing a gate electrode layer over the gate dielectric layer, where the gate electrode layer fills a remainder of gate openings **350**, and performing a planarization process to remove excess gate materials from multigate **200**. For example, a CMP process is performed until a top surface of ILD layer **330** is reached (exposed), such that a top surface of gate structures **300** are substantially planar with a top surface of ILD layer **330** after the CMP process. In FIG. **26**, gate dielectric **382** and gate electrode **384** each extend uninterrupted from n-type transistor region **202A** to p-type transistor region **202B** to n-type transistor region **202C**. Gate dielectric **382** and gate electrode **384** also each extend uninterrupted from first multigate device region **204A** to second multigate device region **204B**. Since metal gate stacks **380** span n-type transistor region **202A**, p-type transistor region **202B**, and n-type transistor region **202C**, metal gate stacks **380** may have different layers in regions corresponding with n-type transistor region **202A**, p-type transistor region **202B**, and n-type transistor region **202C**. For example, a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with p-type transistor region **202B** may be different than a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with n-type transistor region **202A** and/or n-type transistor region **202C**. In another example, a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with n-type transistor region **202A** in first multigate device region

204A may be different than a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with n-type transistor region **202C** in second multigate device region **204B**. In yet another example, a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with p-type transistor region **202B** in first multigate device region **204A** may be different than a number, configuration, and/or materials of layers of gate dielectrics **382** and/or gate electrode **384** corresponding with p-type transistor region **202B** in second multigate device region **204B**.

(48) Gate dielectric **382** partially fills gate openings **350** and wraps channel layers **220'**, such that gate dielectric **382** partially fill gaps **365A** and gaps **365B**. In the depicted embodiment, gate dielectric **382** covers exposed surfaces of channel layers **220'**, such that gate dielectric **382** is disposed along top surfaces, bottom surfaces, and one sidewall of channel layers **220'** (in other words, along three sides of channel layers **220'**). In some embodiments, gate dielectric **382** is further disposed over fin portions **206'**, isolation features **260A**, dielectric fins **280A**, and dielectric fins **280B** in channel regions of multigate device **200**. Gate dielectric **382** includes a high-k dielectric layer, which includes a high-k dielectric material, which for purposes of metal gate stacks **380** refers to a dielectric material having a dielectric constant that is greater than that of silicon dioxide ($k \approx 3.9$). For example, the high-k dielectric layer includes HfO.sub.2, HfSiO, HfSiO.sub.4, HfSiON, HfLaO, HfTaO, HfTiO, HfZrO, HfAlO.sub.x, ZrO, ZrO.sub.2, ZrSiO.sub.2, AlO, AlSiO, Al.sub.2O.sub.3, TiO, TiO.sub.2, LaO, LaSiO, Ta.sub.2O.sub.3, Ta.sub.2O.sub.5, Y.sub.2O.sub.3, SrTiO.sub.3, BaZrO, BaTiO.sub.3 (BTO), (Ba,Sr)TiO.sub.3 (BST), Si.sub.3N.sub.4, hafnium dioxide-alumina (HfO.sub.2—Al.sub.2O.sub.3) alloy, other suitable high-k dielectric material for metal gate stacks, or combinations thereof. The high-k dielectric layer is formed by any of the processes described herein, such as ALD, CVD, PVD, oxidation-based deposition process, other suitable process, or combinations thereof. For example, an ALD process deposits the high-k dielectric layer. In some embodiments, the ALD process is a conformal deposition process, such that a thickness of the high-k dielectric layer is substantially uniform (conformal) over the various surfaces of multigate device **200**. In some embodiments, gate dielectric **382** includes an interfacial layer disposed between the high-k dielectric layer and channel layers **220'**. The interfacial layer includes a dielectric material, such as SiO.sub.2, HfSiO, SiON, other silicon-comprising dielectric material, other suitable dielectric material, or combinations thereof. The interfacial layer is formed by any of the processes described herein, such as thermal oxidation, chemical oxidation, ALD, CVD, other suitable process, or combinations thereof. For example, the interfacial layer is formed by a chemical oxidation process that exposes exposed surfaces of channel layers **220'** to hydrofluoric acid. In some embodiments, the interfacial layer is formed by a thermal oxidation process that exposes the exposed surfaces of channel layers **220'** to an oxygen and/or air ambient. In some embodiments, the interfacial layer is formed after forming the high-k dielectric layer. For example, in some embodiments, after forming the high-k dielectric layer, multigate device **200** may be annealed in an oxygen and/or nitrogen ambient (e.g., nitrous oxide).

(49) Gate electrode **384** is formed over gate dielectric **382**, filling a remainder of gate openings **350** and wrapping channel layers **220'**, such that gate electrode **384** fills a remainder of gaps **365A** and gaps **365B**. In the depicted embodiment, gate electrode **384** is disposed along top surfaces, bottom surfaces, and one sidewall of channel layers **220'** (in other words, along three sides of channel layers **220'**). In some embodiments, gate electrode **384** is further disposed over fin portions **206'**, isolation features **260A**, dielectric fins **280A**, and dielectric fins **280B** in channel regions of multigate device **200**. Gate electrode **384** includes a conductive material, such as polysilicon, aluminum, copper, titanium, tantalum, tungsten, molybdenum, cobalt, TaN, NiSi, CoSi, TiN, WN, TiAl, TiAlN, TaCN, TaC, TaSiN, other conductive material, or combinations thereof. In some embodiments, gate electrode **384** includes a work function layer and a bulk conductive layer. The work function layer is a conductive layer tuned to have a desired work function (e.g., an n-type work function or a p-type work function), and the conductive bulk layer is a conductive layer

formed over the work function layer. In some embodiments, the work function layer includes n-type work function materials, such as Ti, silver, manganese, zirconium, TaAl, TaAlC, TiAlN, TaC, TaCN, TaSiN, other suitable n-type work function materials, or combinations thereof. In some embodiments, the work function layer includes a p-type work function material, such as ruthenium, Mo, Al, TiN, TaN, WN, ZrSi.sub.2, MoSi.sub.2, TaSi.sub.2, NiSi.sub.2, WN, other suitable p-type work function materials, or combinations thereof. The bulk (or fill) conductive layer includes a suitable conductive material, such as Al, W, Ti, Ta, polysilicon, Cu, metal alloys, other suitable materials, or combinations thereof. Gate electrode **284** is formed by any of the processes described herein, such as ALD, CVD, PVD, plating, other suitable process, or combinations thereof.

(50) Turning to FIG. **27**, a self-aligned metal gate cut process is performed that removes portions of metal gate stacks **380** to form metal gates **380A** in first multigate device region **204A** and metal gates **380B** in second multigate device region **204B**, where dielectric fins **280A** separate and isolate metal gates **380A** from metal gates **380B**. Dielectric fins **280A** also separate metal gates **380A** and metal gates **380B** from metal gates and/or other device features in adjacent device regions, such as to the left of first multigate device region **204A** and/or to the right of second multigate device region **204B**. For example, an etch back process is performed to recess gate electrodes **384** until top surfaces of dielectric fins **280A** are free of gate electrodes **384** (i.e., gate electrodes **384** are not disposed over and do not extend over top surfaces of dielectric fins **280A**). The etch back process reopens gate openings **350**. After the etch back process, gate electrodes **384** no longer extend uninterrupted from first multigate device region **204A** to second multigate device region **204B**, thereby forming gate electrodes **384A** in first multigate device region **204A** and gate electrodes **384B** in second multigate device region **204B**, where dielectric fins **280A** separate gate electrodes **384A** and gate electrodes **384B** from one another and from gate electrodes and/or other device features in adjacent multigate device regions. In the depicted embodiment, top surfaces of gate electrodes **384A**, **384B** are lower than top surfaces of dielectric fins **280A** relative to a top surface of substrate **206**. For example, a height difference Δh_2 between topmost surfaces of gate electrodes **384A**, **384B** and topmost surfaces of dielectric fins **280A** (e.g., topmost surfaces of dielectric layers **276**) is about 1 nm to about 10 nm. In some embodiments, top surfaces of gate electrodes **384A**, **384B** are substantially planar with top surfaces of dielectric fins **280A**. In the furtherance of the depicted embodiment, the etch back process does not, or minimally, etches gate dielectrics **382**, such that gate dielectrics **382** still extend uninterrupted from first multigate device region **204A** to second multigate device region **204B**. Accordingly, metal gates **380A** include respective portions of respective gate dielectrics **382** and respective gate electrodes **384A**, and metal gates **380B** include respective portions of respective gate dielectrics **382** and respective gate electrodes **384B**.

(51) The etch back process is configured to selectively remove gate electrodes **384** with respect to gate spacers **299**, ILD layer **330**, CESL **332**, and dielectric layers **276**. In other words, the etch back process substantially removes gate electrodes **384** but does not remove, or does not substantially remove, gate spacers **299**, ILD layer **330**, CESL **332**, and/or dielectric layers **276**. For example, an etchant is selected for the etch process that etches metal materials (e.g., gate electrodes **384**) at a higher rate than dielectric materials (e.g., gate spacers **299**, ILD layer **330**, CESL **332**, dielectric layers **276**, and/or gate dielectrics **232**) (i.e., the etchant has a high etch selectivity with respect to metal materials). The etch back process is a dry etching process, a wet etching process, other suitable etching process, or combinations thereof. In some embodiments, a wet etching process uses a wet etchant solution that can remove metal materials without substantially removing dielectric materials, such as wet etchant solution having a mixture of BCl.sub.3, Cl, and/or HBr. In some embodiments, the etch back process includes multiple steps (for example, each step is configured to etch a particular layer of gate electrodes **384**).

(52) The metal gate cut process is referred to as “self-aligned” because gate isolation structures (here, dielectric fins **280A**, also referred to as gate isolation fins) are aligned between metal gates **380A** and metal gates **380B** without having to perform a lithography process after forming metal

gate stacks **380**. The self-aligned placement of the gate isolation structures provides electrical isolation between devices in adjacent active regions, such as transistors formed in first multigate device region **204A** and transistors formed in second multigate device region **204B**. The self-aligned placement of the gate isolation structures also allows for higher packing density without negatively affecting operation of closely spaced devices in a high-density IC. For example, a spacing **S3** between an active region (e.g., fin portion **206'**) of first multigate device region **204A** and an active region (e.g., fin portion **206'**) of second multigate device region **204B** can be smaller than spacings required between active regions of adjacent multigate device regions when implementing non-self-aligned metal gate cut techniques, which often require a lithography process to form the gate isolation structures. In some embodiments, spacing **S3** is about 20 nm. Smaller spacings between active regions are possible because the proposed self-aligned metal gate cut technique does not suffer from overlay issues associated with non-self-aligned metal gate cut techniques. Smaller spacings between active regions can thus be implemented without risking unintentional damage to channel layers **220'**, metal gates **380A**, and/or metal gates **380B**, which damage can arise from process variations inherent in non-self-aligned metal gate cut techniques. Different embodiments may have different advantages, and no particular advantage is necessarily required of any embodiment.

(53) Turning to FIG. **28**, a metal capping layer **390A** is formed over metal gate **380A**, a metal capping layer **390B** is formed over metal gate **380B**, and dielectric layers **392** are formed over metal capping layers **390A**, **390B**. Metal capping layer **390A**, metal capping layer **390B**, and dielectric layer **392** fill remainders of gate openings **350**, such that metal capping layers **390A**, **390B** and dielectric layers **392** are disposed between gate spacers **299** of gate structures **300**. Dielectric layers **392** extend over top surfaces of dielectric fins **280A**, such that dielectric layers **392** extend uninterrupted from first multigate device region **204A** to second multigate device region **204B**. In the depicted embodiment, gate dielectrics **382** separate dielectric layers **392** from dielectric fins **280A**. In some embodiments, where gate dielectrics **382** are removed from top surfaces of dielectric fins **280A**, for example, during the etch back process in FIG. **27**, dielectric layers **392** may directly, physically contact dielectric fins **280A** (in particular, dielectric layers **276**). Metal capping layers **390A**, **390B** include a metal material and are formed by any suitable process, such as those described herein. In some embodiments, metal capping layers **390A**, **390B** are formed by a deposition process that selectively grows a metal layer from metal surfaces (i.e., gate electrodes **384A**, **384B**) without growing the metal layer on dielectric surfaces (i.e., gate dielectrics **382**, gate spacers **299**, ILD layer **330**, and/or CESL **332**). In some embodiments, metal capping layers **390A**, **390B** include tungsten and are referred to as tungsten layers. Dielectric layers **392** include a dielectric material and are formed by any suitable process, such as those described herein. The dielectric material can include silicon, oxygen, carbon, nitrogen, other suitable material, or combinations thereof (for example, silicon oxide, silicon nitride, silicon oxynitride, silicon carbide, and/or silicon oxycarbonitride). In the depicted embodiment, dielectric layers **392** include silicon and nitrogen, such as a silicon nitride layer. In some embodiments, dielectric layers **392** are formed by depositing the dielectric material over multigate device **200**, where the dielectric material fills gate openings **350**, and performing a planarization process to remove the dielectric material from over ILD layer **330**.

(54) Fabrication can then proceed with forming various contacts, such as gate contacts and source/drain contacts to facilitate operation of transistors of multigate device **200**. Turning to FIGS. **29A-29D**, source/drain contacts **400** are formed to epitaxial source/drain features **320A**, **320B**. For case of description and understanding, FIG. **29A** is taken (cut) through one of gate structures **300** along line G-G' in FIG. **20** after undergoing processing associated with FIGS. **21-28** and FIGS. **29A-29D** (and can be referred to as metal gate cut perspective view), FIG. **29B** is taken (cut) through one of gate structures **300** along line H-H' in FIG. **20** after undergoing processing associated with FIGS. **21-28** and FIGS. **29A-29D** (and can be referred to as a source/drain cut

perspective view); FIG. 29C is a cross-sectional view along line G-G' in FIG. 20 after undergoing processing associated with FIGS. 21-28 and FIGS. 29A-29D (and can be referred to as a metal gate cut cross-sectional view); and FIG. 29D is a cross-sectional view along line H-H' in FIG. 20 after undergoing processing associated with FIGS. 21-26 and FIGS. 29A-29D (and can be referred to as a source/drain cross-sectional view). In FIGS. 29A-29D, source/drain contacts 400 extend through an ILD layer 408, a CESL 410, ILD layer 330, and CESL 332 to epitaxial source/drain features 320A, 320B. In some embodiments, source/drain contacts 400 are formed by depositing CESL 410 over multigate device 200 (in particular, over gate contacts 390, CESL 332, ILD layer 330, and gate spacers 299), depositing ILD layer 408 over CESL 410, patterning ILD layers and/or CESLs (e.g., ILD layers 408, 330 and/or CESLs 410, 332) to form source/drain contact openings, and filling source/drain contact openings with a conductive material. Patterning ILD layers 408, 330 and/or CESLs 410, 332 can include lithography processes and/or etching processes. In some embodiments, the lithography processes include forming a resist layer over respective ILD layer 408, exposing the resist layer to patterned radiation, and developing the exposed resist layer, thereby forming a patterned resist layer that can be used as a masking element for etching source/drain contact opening(s) that extend through ILD layer 408, CESL 410, ILD layer 330, and CESL 332 to expose epitaxial source/drain features 320A, 320B. The etching processes include dry etching processes, wet etching processes, other etching processes, or combinations thereof. Thereafter, the source/drain contact opening(s) are filled with one or more electrically conductive materials, such as tungsten, ruthenium, cobalt, copper, aluminum, iridium, palladium, platinum, nickel, other low resistivity metal constituent, alloys thereof, or combinations thereof. The conductive material(s) can be deposited by PVD, CVD, ALD, electroplating, electroless plating, other suitable deposition process, or combinations thereof. In some embodiments, source/drain contacts 400 include a bulk layer (also referred to as a conductive plug). In some embodiments, source/drain contacts 400 include a barrier layer, an adhesion layer, and/or other suitable layer disposed between the bulk layer and ILD layers 408, 330 and/or CESLs 410, 332. In such embodiments, the barrier layer and/or the adhesion layer conform to the source/drain contact openings, such that the barrier layer and/or the adhesion layer is disposed on ILD layers 408, 330 and/or CESLs 410, 332 and the bulk layer is disposed on the barrier layer and/or the adhesion layer. In some embodiments, the barrier layer, the adhesion layer, and/or other suitable layer include titanium, titanium alloy (for example, TiN), tantalum, tantalum alloy (for example, TaN), other suitable constituent, or combinations thereof. Thereafter, any excess conductive material(s) can be removed by a planarization process, such as a CMP process, thereby planarizing a top surface of ILD layer 408 and top surfaces of epitaxial source/drain features.

(55) Accordingly, multigate device 200 includes first CMOS transistors in first multigate device region 204A and second CMOS transistors in second multigate device region 204B. The first CMOS transistors have metal gates 380A (each of which includes a respective portion of a respective gate dielectric 382 and a respective gate electrode 384A) and metal capping layer 390A, and the second CMOS transistors have metal gates 380B (each of which includes a respective portion of a respective gate dielectric 382 and a respective gate electrode 384B) and metal capping layer 390B. Metal capping layers 390A, 390B can be considered a portion of metal gates 380A, 380B, respectively, in some embodiments. Each first CMOS transistor includes an n-type transistor in n-type transistor region 202A and a p-type transistor in p-type transistor region 202B, where the n-type transistor includes a first portion of metal gate 380A and respective epitaxial source/drain features 320A and the p-type transistor includes a second portion of metal gate 380A and respective epitaxial source/drain features 320B. The first portion of metal gate 380A wraps respective channel layers 220' and is disposed between its respective epitaxial source/drain features 320A. The second portion of metal gate 380A wraps respective channel layers 220' and is disposed between its respective epitaxial source/drain features 320B. In a similar manner, each second CMOS transistor includes a p-type transistor in p-type transistor region 202B and an n-type transistor in n-type

transistor region **202C**, where the p-type transistor includes a first portion of metal gate **380B** and respective epitaxial source/drain features **320B** and the n-type transistor includes a second portion of metal gate **380B** and respective epitaxial source/drain features **320A**. The first portion of metal gate **380B** wraps respective channel layers **220'** and is disposed between its respective epitaxial source/drain features **320A**. The second portion of metal gate **380B** wraps respective channel layers **220'** and is disposed between its respective epitaxial source/drain features **320B**.

(56) Dielectric fins **280A** separate and isolate the first CMOS transistors from the second CMOS transistors. The first portions of metal gates **380A**, **380B** are separated from the second portions of metal gates **380A**, **380B** by respective ones of second portions **280B-2** of dielectric fins **280B**. Different types of dielectric fins separate different multigate devices and different devices within the different multigate devices. Because of the different types of dielectric fins used for isolation and separation, the n-type transistors and the p-type transistors of the first CMOS transistors and the second CMOS transistors have metal gates with asymmetric profiles. For example, first portion of metal gate **380A**, second portion of metal gate **380A**, first portion of metal gate **380B**, and second portion of metal gate **380B** are disposed along a first sidewall of their respective channel layers **220'**, but not along a second sidewall of their respective channel layers **220'**, where a width of the respective channel layers **220'** is defined between the first sidewall and the second sidewall. Instead, the second sidewall of their respective channel layers **220'** physically contacts a respective one of first portions **280B-1** of dielectric fins **280B**. First portion of metal gate **380A**, second portion of metal gate **380A**, first portion of metal gate **380B**, and second portion of metal gate **380B** thus partially, instead of completely, surround their respective channel layers **220'**. In particular, first portion of metal gate **380A**, second portion of metal gate **380A**, first portion of metal gate **380B**, and second portion of metal gate **380B** each covers three sides of their respective channel layers **220'**.

(57) Width differences between dielectric fins **280A** and **280B** cause lateral growth variations of epitaxial source/drain features **320A**, **320B** along the x-direction, which results in epitaxial source/drain features **320A**, **320B** having asymmetric profiles. For example, each of epitaxial source/drain features **320A**, **320B** has a facet A that physically contacts a respective one of first portions **280B-1** of dielectric fins **280B**, a facet B that physically contacts a respective one of dielectric fins **280B**, a facet C that extends from facet A to a respective one of fin portions **206'**, a facet D that extends from facet B to a respective one of fin portions **206'**, a facet E that extends from facet A to a facet F (e.g., top surfaces of epitaxial source/drain features **320A**, **320B**), and a facet G that extends from facet B to facet F. Because a width of dielectric fins **280A** is less than a width of their underlying isolation features (e.g., isolation features **260A**) but a width of dielectric fins **280B** is substantially the same as a width of their underlying isolation features (e.g., isolation features **260B**), such that sidewalls of dielectric fins **280A** are spaced away from sidewalls of fin portions **206'** along the x-direction while sidewalls of dielectric fins **280B** are not spaced away from sidewalls of fin portions **206'** along the x-direction, epitaxial material can grow laterally along the x-direction beyond a first sidewall of the respective one of the fin portions **206'** from which it grows but not beyond a second sidewall of the respective one of the fin portions **206'** from which it grows. Such lateral growth variation results in length variations between facets proximate and adjacent to dielectric fins **280A** and facets proximate and adjacent to dielectric fins **280B**. In FIGS. **29A-29C**, a length of facet A is greater than a length of facet B and lengths of facets that extend from facet A (e.g., facet C and facet E) are less than lengths of facets that extend from facet B (e.g., facet D and facet G). Facets of epitaxial source/drain features **320A**, **320B** extending from dielectric fins **280A** are thus longer and larger than facets of epitaxial source/drain features **320A**, **320B** extending from dielectric fins **280B**. Further, in some embodiments, air gaps **412** are formed between facets D, dielectric fins **280A**, and isolation features **260A**, while air gaps are not formed between facets C, dielectric fins **280B**, and isolation features **260B**. In some embodiments, where air gaps are formed between facets C, dielectric fins **280B**, and isolation features **260B**, such a

volume and/or a size of such air gaps is smaller than a volume and/or a size of air gaps **412** because of the lateral growth variations caused by width differences in dielectric fins **280A**, **280B**.

(58) Though not depicted, one or more gate contacts can be formed that extend through ILD layer **408**, CESL **410**, and dielectric layer **392** to metal gate **380A** and/or metal gate **380B**. In some embodiments, the gate contacts extend into or through metal capping layers **390A**, **390B**. A gate contact can include a contact barrier layer and a contact plug disposed over the contact barrier layer. The contact barrier layer includes a material that promotes adhesion between a surrounding dielectric material (here, ILD layer **408**, CESL **410**, dielectric layers **392**, and/or other ILD layers, CESL layers, and/or dielectric layers formed over ILD layer **408**) and the contact plug. The material of the contact barrier layer may further prevent diffusion of metal constituents from the contact plug into the surrounding dielectric material. In some embodiments, the contact barrier layer includes titanium, titanium alloy, tantalum, tantalum alloy, cobalt, cobalt alloy, ruthenium, ruthenium alloy, molybdenum, molybdenum alloy, palladium, palladium alloy, other suitable constituent configured to promote and/or enhance adhesion between a metal material and a dielectric material and/or prevent diffusion of metal constituents from the metal material to the dielectric material, or combinations thereof. For example, the contact barrier layer includes tantalum, tantalum nitride, tantalum aluminum nitride, tantalum silicon nitride, tantalum carbide, titanium, titanium nitride, titanium silicon nitride, titanium aluminum nitride, titanium carbide, tungsten, tungsten nitride, tungsten carbide, molybdenum nitride, cobalt, cobalt nitride, ruthenium, palladium, or combinations thereof. In some embodiments, the contact barrier layer includes multiple layers. For example, the contact barrier layer may include a first sub-layer that includes titanium and a second sub-layer that includes titanium nitride. In another example, the contact barrier layer may include a first sub-layer that includes tantalum and a second sub-layer that includes tantalum nitride. The contact plug includes tungsten, ruthenium, cobalt, copper, aluminum, iridium, palladium, platinum, nickel, low resistivity metal constituent, alloys thereof, or combinations thereof. The gate contacts can be formed using a damascene process, a dual damascene process, any of the processes described herein, and/or other suitable process.

(59) The various etching processes performed in FIGS. **2-28** and FIGS. **29A-29D** include dry etching processes, wet etching processes, or combinations thereof. The dry etching processes may implement a hydrogen-comprising etch gas (e.g., H.sub.2 and/or CH.sub.4), a nitrogen-comprising etch gas (for example, N.sub.2 and/or NH.sub.3), a chlorine-comprising etch gas (for example, Cl.sub.2, CHCl.sub.3, CCl.sub.4, and/or BCl.sub.3), an oxygen-comprising etch gas (for example, O.sub.2), a fluorine-comprising etch gas (for example, F.sub.2, CH.sub.3F, CH.sub.2F.sub.2, CHF.sub.3, CF.sub.4, C.sub.2F.sub.6, SF.sub.6, and/or NF.sub.3), a bromine-comprising etch gas (e.g., Br, HBr, CH.sub.3Br, CH.sub.2Br.sub.2, and/or CHBr.sub.3), an iodine-comprising etch gas, other suitable etch gas, or combinations thereof. The dry etching processes can use a carrier gas to deliver the etch gas. The carrier gas can include nitrogen, argon, helium, xenon, other suitable carrier gas constituent, or combinations thereof. The wet etching processes may implement a wet etchant solution that includes H.sub.2SO.sub.4, H.sub.2O.sub.2, NH.sub.4OH, HCl, HF, DHF, KOH, NH.sub.3, CH.sub.3COOH, HNO.sub.3, H.sub.3PO.sub.4, H.sub.2O (which can be DIW or DIWO.sub.3), O.sub.3, other suitable chemicals, or combinations thereof. During each etching process, various etch parameters can be tuned to achieve desired selective etching, such as a flow rate of an etch gas, a concentration of the etch gas, a concentration of the carrier gas, a ratio of a concentration of a first etch gas to a concentration of a second etch gas, a ratio of the concentration of the carrier gas to the concentration of the etch gas, a concentration of a wet etch solution, a ratio of a concentration of a first wet etch constituent to a concentration of a second wet etch constituent, a power of an RF source, a bias voltage, a pressure, a duration of the etch process, a temperature maintained in a process chamber during the etch process, a temperature of a wafer during the etch process, a temperature of the wet etch solution, other suitable etch parameters, or combinations thereof. Further, the various etching processes described herein can include multiple steps.

(60) From the foregoing description, it can be seen that multigate devices described in the present disclosure offer advantages over conventional multigate devices. It is understood, however, that other embodiments may offer additional advantages, and not all advantages are necessarily disclosed herein, and that no particular advantage is required for all embodiments. One advantage is that fabrication processes described herein reduce a size and/or a footprint of metal gates and epitaxial source/drain features of transistors, compared to transistors fabricated using conventional metal gate cut techniques, thereby allowing for higher packing density of transistors and increasing IC pattern density. Reduced sizes and/or footprints of the metal gates and epitaxial source/drain features arise because dielectric fins **280A**, **280B** confine space for forming such features. Another advantage from the reduced sizes and/or footprints is a reduction in parasitic capacitance. For example, smaller metal gates and epitaxial source/drain features reduces parasitic capacitance (C_{gd}) between the metal gates and the source/drain features, thereby improving speed and performance of transistors. Furthermore, as described above, the disclosed self-aligned metal gate cut techniques described herein do not have to account for lithography process variations, allowing for smaller spacings between active regions of transistors, and thus further increasing packing density of transistors and IC pattern density.

(61) The present disclosure provides for many different embodiments. An exemplary device includes a substrate and a multigate device having a channel layer, a metal gate that wraps a portion of the channel layer, and source/drain features disposed over the substrate. The channel layer extends along a first direction between the source/drain features. The device further includes a first dielectric fin and a second dielectric fin disposed over the substrate. The channel layer extends along a second direction between the first dielectric fin and the second dielectric fin. The second direction is different than the first direction. The metal gate is disposed between the channel layer and the second dielectric fin. The first dielectric fin is different than the second dielectric fin. In some embodiments, the device further includes a first isolation feature disposed between the first dielectric fin and the substrate and a second isolation feature disposed between the second dielectric fin and the substrate. The second isolation feature is different than the first isolation feature. In some embodiments, the metal gate is disposed over and physically contacts a top surface of the first dielectric fin. In some embodiments, a top surface of the first dielectric fin relative to a top surface of the substrate is lower than a top surface of the metal gate relative to the top surface of the substrate. In some embodiments, a top surface of the second dielectric fin relative to the top surface of the substrate is higher than the top surface of the metal gate relative to the substrate.

(62) In some embodiments, the first dielectric fin includes a first oxide layer and a first dielectric layer having a first dielectric constant and the second dielectric fin includes a second oxide layer, a second dielectric layer having the first dielectric constant, and a third dielectric layer having a second dielectric constant that is greater than the first dielectric constant. The first oxide layer is disposed over the first dielectric layer, the second oxide layer is disposed over the second dielectric layer, and the third dielectric layer is disposed over the second oxide layer. In some embodiments, the first isolation feature includes a first oxide layer and a dielectric liner, where the first oxide layer is disposed over the dielectric liner, and the second isolation feature includes a second oxide layer. In some embodiments, a first silicon liner is disposed between the substrate and the dielectric liner, and a second silicon liner is disposed between the substrate and the second oxide layer. In some embodiments, the device further includes a gate contact that wraps a portion of the third dielectric layer of the second dielectric fin.

(63) In some embodiments, the multigate device is a first multigate device, the channel layer is a first channel layer, the metal gate is a first metal gate, and the source/drain features are first source/drain features. In such embodiments, the device can further include a third dielectric fin disposed over the substrate and a second multigate device having a second channel layer, a second metal gate wrapping a portion of the second channel layer, and second source/drain features disposed over the substrate. The second channel layer extends along the first direction between the

second source/drain features. The second dielectric fin is disposed between and separates the first metal gate and the second metal gate. The second channel layer extends along the second direction between the second dielectric fin and the third dielectric fin. The second metal gate is disposed between the second channel layer and the third dielectric fin. The third dielectric fin is the same as the first dielectric fin.

(64) Another exemplary device includes a fin portion disposed between a first isolation feature and a second isolation feature. The first isolation feature is different than the second isolation feature. The device further includes a first dielectric fin disposed over the first isolation feature and a second dielectric fin disposed over the second isolation feature. The first dielectric fin is different than the second dielectric fin. The device further includes a multigate device having a channel layer, a metal gate that wraps a portion of the channel layer, and source/drain features. The channel layer extends along a first direction between the source/drain features and along a second direction between the first dielectric fin and the second dielectric fin. The second direction is different than the first direction. The metal gate is disposed between and separates the channel layer from the second dielectric fin.

(65) In some embodiments, the channel layer has a top surface, a bottom surface, a first sidewall that extends between the top surface and the bottom surface, and a second sidewall that extends between the top surface and the bottom surface. The metal gate physically contacts the top surface, the bottom surface and the first sidewall and the first dielectric fin physically contacts the second sidewall. In some embodiments, the first dielectric fin has a first width along the second direction, the second dielectric fin has a second width along the second direction, the first isolation feature has a third width along the second direction, and the second isolation feature has a fourth width along the second direction. The first width is substantially the same as the third width and the second width is less than the fourth width.

(66) In some embodiments, the first dielectric fin includes a first oxide layer and a first dielectric layer, where the first oxide layer is disposed over the first dielectric layer. In such embodiments, the second dielectric fin includes a second oxide layer, a second dielectric layer, and a third dielectric layer, where the second oxide layer is disposed over the second dielectric layer and the third dielectric layer is disposed over the second oxide layer. In such embodiments, the first isolation feature includes a third oxide layer and a fourth dielectric layer, where the third oxide layer is disposed over the fourth dielectric layer. In such embodiments, the second isolation feature includes a fourth oxide layer. The first dielectric layer, the second dielectric layer, and the fourth dielectric layer have a first dielectric constant. The third dielectric layer has a second dielectric constant that is greater than the first dielectric constant. In some embodiments, the first dielectric layer, the second dielectric layer, and the fourth dielectric layer each include a silicon-comprising dielectric material and the third dielectric layer includes a metal-and-oxygen comprising dielectric material. In some embodiments, the first isolation feature further includes a first silicon layer disposed between the fourth dielectric layer and the fin portion and the second isolation feature further includes a second silicon layer disposed between the fourth oxide layer and the fin portion.

(67) In some embodiments, the first dielectric fin has a first portion in a channel region of the device and second portions in source/drain regions of the device. A first configuration of the first portion is different than a second configuration of the second portions. In such embodiments, the second dielectric fin has a third portion in the channel region of the device and fourth portions in the source/drain regions of the device. A third configuration of the third portion is different than a fourth configuration of the fourth portions. The channel layer extends along the second direction between the first portion of the first dielectric fin and the third portion of the second dielectric fin. The source/drain features extend along the second direction between the second portions of the first dielectric fin and the fourth portions of the second dielectric fin. Each of the source/drain features have a first facet disposed along a respective one of the second portions of the first dielectric fin and a second facet disposed along a respective one of the fourth portions of the second dielectric

fin. In some embodiments, a first length of the first facet is greater than a second length of the second facet. In some embodiments, a third facet extends from the first facet and a fourth facet extends from the second facet. In some embodiments, a third length of the third facet is less than a fourth length of the fourth facet.

(68) An exemplary method includes forming a multigate device having a channel layer, a metal gate that wraps a portion of the metal gate, and source/drain features over a substrate. The channel layer extends along a first direction between the source/drain features. The method further includes forming a first dielectric fin and a second dielectric fin over the substrate. The channel layer extends along a second direction between the first dielectric fin and the second dielectric fin. The second direction is different than the first direction. The metal gate is disposed between the channel layer and the second dielectric fin. The first dielectric fin is different than the second dielectric fin. In some embodiments, the method further includes forming a first isolation feature and a second isolation feature before forming the first dielectric fin and the second dielectric fin. The first dielectric fin is disposed over the first isolation feature and the second dielectric fin is disposed over the second isolation feature. The first isolation feature is different than the second isolation feature. In some embodiments, the method further includes forming an interlevel dielectric layer over the multigate device, the first dielectric fin, and the second dielectric fin. In some embodiments, the multigate device is a first multigate device and the metal gate is a first metal gate, and the method further includes performing a gate cut process that separates the first metal gate from a second metal gate of a second multigate device without performing a lithography process.

(69) Another exemplary method includes forming a first fin structure, a second fin structure, a third fin structure, and a fourth fin structure over a substrate. A first trench is defined between the first fin structure and the second fin structure, a second trench is defined between the second fin structure and the third fin structure, and a third trench is defined between the third fin structure and the fourth fin structure. The first fin structure, the second fin structure, the third fin structure, and the fourth fin structure each include a first semiconductor layer disposed over a second semiconductor layer. The method further includes forming a silicon liner over the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure. The silicon liner lines the first trench, the second trench, and the third trench. The method further includes forming a dielectric liner over the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure. The dielectric liner is disposed over the silicon liner and further lines the first trench, the second trench, and the third trench. The method further includes, after removing the dielectric liner from the second trench, filling the first trench, the second trench, and the third trench with an oxide material.

(70) The method further includes partially removing the oxide material and the dielectric liner to form a first isolation feature between the first fin structure and the second fin structure, a second isolation feature between the second fin structure and the third fin structure, and a third isolation feature between the third fin structure and the fourth fin structure. The first isolation feature includes a first oxide layer disposed over a first dielectric liner, the second isolation feature includes a second oxide layer, the third isolation feature includes a third oxide layer disposed over a second dielectric liner. The first isolation feature, the second isolation feature, and the third isolation feature fill a respective lower portion of the first trench, the second trench, and the third trench. The method further includes forming a first dielectric fin over the first isolation feature, a second dielectric fin over the second isolation feature, and a third dielectric fin over the third isolation feature. The first dielectric fin includes a fourth oxide layer disposed over a first low-k dielectric layer and a first high-k dielectric layer disposed over the fourth oxide layer, the second dielectric fin includes a fifth oxide layer disposed over a second low-k dielectric layer and a second high-k dielectric layer disposed over the fifth oxide layer, and the third dielectric fin includes a sixth oxide layer disposed over a third low-k dielectric layer and a third high-k dielectric layer

disposed over the sixth oxide layer. The first dielectric fin, the second dielectric fin, and the third dielectric fin fill a respective upper portion of the first trench, the second trench, and the third trench.

(71) The method further includes, after removing a mask layer of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure, forming a dummy gate structure over channel regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure. The dummy gate structure includes a dummy gate and gate spacers. The dummy gate wraps first portions of the first high-k dielectric layer of the first dielectric fin, the second high-k dielectric layer of the second dielectric fin, and the third high-k dielectric layer of the third dielectric fin. The channel regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure are disposed between respective source/drain regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure. The method further includes etching the source/drain regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure to form source/drain recesses. In some embodiments, the etching recesses the first high-k dielectric layer, the second high-k dielectric layer, and the third high-k dielectric layer respectively of second portions of the first dielectric fin, the second dielectric fin, and the third dielectric fin that are not covered by the dummy gate structure. The method further includes forming first source/drain features in the source/drain recesses of the first fin structure and the fourth fin structure and second source/drain features in the source/drain recesses of the second fin structure and the third fin structure. The method can further include forming inner spacers before forming the first source/drain features and the second source/drain features.

(72) The method further includes forming an interlevel dielectric (ILD) layer over the first source/drain features, the second source/drain features, and the second portions of the first dielectric fin, the second dielectric fin, and the third dielectric fin that are not covered by the dummy gate structure. The method further includes partially removing the dummy gate to form a gate opening, wherein the gate opening exposes the first high-k dielectric layer, the second high-k dielectric layer, and the third high-k dielectric layer respectively of the first portions of the first dielectric fin, the second dielectric fin, and the third dielectric fin. The method further includes masking the second high-k dielectric layer of the first portion of the second dielectric fin and removing the first high-k dielectric layer and the third high-k dielectric layer respectively from the first portions of the first dielectric fin and the third dielectric fin. The method further includes removing a remainder of the dummy gate, such that the gate opening further exposes channel regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure. The method further includes selectively removing the second semiconductor layer from the channel regions of the first fin structure, the second fin structure, the third fin structure, and the fourth fin structure, such that the first semiconductor layer in the channel region of the first fin structure is suspended to provide a first channel layer, the first semiconductor layer in the channel region of the second fin structure is suspended to provide a second channel layer, the first semiconductor layer in the channel region of the third fin structure is suspended to provide a third channel layer, and the first semiconductor layer in the channel region of the fourth fin structure is suspended to provide a fourth channel layer. The first dielectric fin is disposed between the first channel layer and the second channel layer, the second dielectric fin is disposed between the second channel layer and the third channel layer, and the third dielectric fin is disposed between the third channel layer and the fourth channel layer.

(73) The method further includes forming a first metal gate in the gate opening that wraps the first channel layer and the second channel layer and a second metal gate in the gate opening that wraps the third channel layer and the fourth channel layer. The first metal gate is disposed between the second channel layer and the second dielectric fin and the second metal gate is disposed between the third channel layer and the second dielectric fin. In some embodiments, forming the first metal

gate in the gate opening and the second metal gate in the gate opening includes depositing a gate dielectric layer over the first channel layer, the second channel layer, the third channel layer, and the fourth channel layer that partially fills the gate opening. In such embodiments, forming the first metal gate in the gate opening and the second metal gate in the gate opening further includes depositing a gate electrode layer over the gate dielectric layer, wherein the gate electrode layer fills a remainder of the gate opening and the gate electrode layer extends over a top surface of the second high-k dielectric layer of the first portion of the second dielectric fin. In such embodiments, forming the first metal gate in the gate opening and the second metal gate in the gate opening further includes recessing the gate electrode layer to expose the top surface of the second high-k dielectric layer of the first portion of the second dielectric fin, thereby forming a first gate electrode that wraps the first channel layer and the second channel layer and a second gate electrode that wraps the third channel layer and the fourth channel layer. The first gate electrode is separated from the second gate electrode by the first portion of the second dielectric fin. The method further includes forming a gate contact in a remainder of the gate opening, where the gate contact is disposed over the first metal gate and the second metal gate. The method further includes forming first source/drain contacts that extend through the ILD layer to the first source/drain features and second source/drain contacts that extend through the ILD layer to the second source/drain features.

(74) Another exemplary device includes a substrate, a first dielectric fin and a second dielectric fin disposed over the substrate, and a multigate device having a channel layer, a metal gate the wraps a portion of the channel layer, and source/drain features disposed over the substrate. The channel layer extends along a first direction between the source/drain features. The channel layer further extends along a second direction from the first dielectric fin to the metal gate. The second direction is different than the first direction. The metal gate is disposed between the channel layer and the second dielectric fin. The first dielectric fin is different than the second dielectric fin. In some embodiments, the device further includes a first isolation feature disposed between the first dielectric fin and the substrate and a second isolation feature disposed between the second dielectric fin and the substrate. The second isolation feature is different than the first isolation feature. In some embodiments, the metal gate is disposed over a top surface of the first dielectric fin. In some embodiments, a top surface of the first dielectric fin relative to a top surface of the substrate is lower than a top surface of the metal gate relative to the top surface of the substrate, and a top surface of the second dielectric fin relative to the top surface of the substrate is higher than the top surface of the metal gate relative to the substrate.

(75) In some embodiments, the first dielectric fin includes a first oxide layer and a first low-k dielectric layer, and the second dielectric fin includes a second oxide layer, a second low-k dielectric layer, and a high-k dielectric layer. The first oxide layer is disposed over the first low-k dielectric layer. The second oxide layer is disposed over the second low-k dielectric layer and the high-k dielectric layer is disposed over the second oxide layer. In some embodiments, the device further includes a gate contact that wraps a portion of the high-k dielectric layer. In some embodiments, the first isolation feature includes a first oxide layer and a dielectric liner, where the first oxide layer is disposed over the dielectric liner, and the second isolation feature includes a second oxide layer. In some embodiments, the device further includes a first silicon liner disposed between the substrate and the dielectric liner and a second silicon liner disposed between the substrate and the second oxide layer. In some embodiments, the substrate includes a fin portion disposed between the first isolation feature and the second isolation feature, the channel layer is disposed over the fin portion, and the metal gate is disposed between the fin portion and the channel layer. In some embodiments, the first dielectric fin has a first width along the second direction, the second dielectric fin has a second width along the second direction, the first isolation feature has a third width along the second direction, the second isolation feature has a fourth width along the second direction, the first width is substantially the same as the third width, and the second width is less than the fourth width.

(76) In some embodiments, the device further includes a third dielectric fin and a fourth dielectric fin disposed over the substrate. The source/drain features extend along the second direction from the third dielectric fin to the fourth dielectric fin. The third dielectric fin and the fourth dielectric fin each include an oxide layer, a low-k dielectric layer, and a high-k dielectric layer. The oxide layer is disposed over the low-k dielectric layer and the high-k dielectric layer is disposed over the oxide layer. In some embodiments, the source/drain features have a first sidewall disposed along the third dielectric fin, a second sidewall disposed along the fourth dielectric fin, a first facet that extends from the first sidewall, a second facet that extends from the second sidewall. In some embodiments, a first length of the first sidewall is greater than a second length of the second sidewall and a third length of the first facet is less than a fourth length of the second facet. In some embodiments, the third dielectric fin has a first width along the second direction and the fourth dielectric fin has a second width along the second direction, wherein the first width is greater than a second width.

(77) In some embodiments, the multigate device is a first multigate device, the channel layer is a first channel layer, the metal gate is a first metal gate, and the source/drain features are first source/drain features. In such embodiments, the device further includes a second multigate device having a second channel layer, a second metal gate wrapping a portion of the second metal gate, and second source/drain features disposed over the substrate. The second channel layer extends along the first direction between the second source/drain features. In such embodiments, the device can further include a third dielectric fin disposed over the substrate. The second dielectric fin is disposed between and separates the first metal gate and the second metal gate. The second channel layer further extends along the second direction from the third dielectric fin to the second metal gate. The second metal gate is disposed between the second channel layer and the second dielectric fin. In some embodiments, the third dielectric fin is the same as the first dielectric fin.

(78) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A device structure comprising: a first semiconductor layer and a second semiconductor layer disposed over a base structure, wherein the first semiconductor layer is disposed in a first device region and the second semiconductor layer is disposed in a second device region; a first gate isolation structure, a second gate isolation structure, and a third gate isolation structure, wherein the second gate isolation structure is disposed between the first gate isolation structure and the third gate isolation structure, the first gate isolation structure and the third gate isolation structure have a first configuration, the second gate isolation structure has a second configuration, and the second configuration is different than the first configuration; and a gate disposed over the first semiconductor layer and the second semiconductor layer, wherein in a cross-sectional view along a gate lengthwise direction, the gate has: a first portion that extends from the first gate isolation structure over the first semiconductor layer, over the second gate isolation structure, and over the second semiconductor layer to the third gate isolation structure, a second portion that extends from the first gate isolation structure to the second gate isolation structure, a third portion that extends from the second gate isolation structure to the third gate isolation structure a fourth portion that extends from the first gate isolation structure to the first semiconductor layer, wherein the first semiconductor layer extends from the fourth portion to the second gate isolation structure, and a

fifth portion that extends from the second semiconductor layer to the third gate isolation structure, wherein the second semiconductor layer extends from the fifth portion to the second gate isolation structure.

2. The device structure of claim 1, wherein: the first gate isolation structure and the third gate isolation structure have a first height; the second gate isolation structure has a second height; and the first height is greater than the second height.

3. The device structure of claim 1, wherein: the first gate isolation structure and the third gate isolation structure have a first width; the second gate isolation structure has a second width; and the first width is less than the second width.

4. The device structure of claim 1, further comprising: a first substrate isolation structure, a second substrate isolation structure, and a third substrate isolation structure, wherein the second substrate isolation structure is disposed between the first substrate isolation structure and the third substrate isolation structure; the first gate isolation structure is disposed over the first substrate isolation structure, the second gate isolation structure is disposed over the second substrate isolation structure, and the third gate isolation structure is disposed over the third substrate isolation structure; and the first substrate isolation structure and the third substrate isolation structure have a third configuration, the second substrate isolation structure has a fourth configuration, and the third configuration is different than the first configuration.

5. The device structure of claim 4, wherein: the base structure includes a third semiconductor layer and a fourth semiconductor layer, wherein the third semiconductor layer is disposed between the first substrate isolation structure and the second substrate isolation structure and the fourth semiconductor layer is disposed between the second substrate isolation structure and the third substrate isolation structure; the first semiconductor layer is disposed over the third semiconductor layer; and the second semiconductor layer is disposed over the fourth semiconductor layer.

6. The device structure of claim 5, wherein: the gate has a sixth portion that extends from the first gate isolation structure to the second gate isolation structure, wherein the sixth portion is disposed on the first substrate isolation structure and the third semiconductor layer; and the gate has a seventh portion that extends from the second gate isolation structure to the third gate isolation structure, wherein the seventh portion is disposed on the second substrate isolation structure and the fourth semiconductor layer.

7. The device structure of claim 4, wherein: the gate has a sixth portion that extends from the first gate isolation structure to the second gate isolation structure, wherein the sixth portion is disposed on the first substrate isolation structure; and the gate has a seventh portion that extends from the second gate isolation structure to the third gate isolation structure, wherein the seventh portion is disposed on the second substrate isolation structure.

8. The device structure of claim 4, wherein: the first gate isolation structure and the third gate isolation structure have a first width; and the first substrate isolation structure and the third substrate isolation structure have a second width that is greater than the first width.

9. The device structure of claim 8, wherein the second gate isolation structure and the second substrate isolation structure have a third width.

10. The device structure of claim 1, wherein: the fourth portion is connected to the first portion and the second portion; and the fifth portion is connected to the first portion and the third portion.

11. A device structure comprising: a base structure including a first semiconductor layer and a second semiconductor layer, wherein the first semiconductor layer is disposed in a first device region and the second semiconductor layer is disposed in a second device region; a first source/drain isolation structure, a second source/drain isolation structure, and a third source/drain isolation structure, wherein the second source/drain isolation structure is disposed between the first source/drain isolation structure and the third source/drain isolation structure, the first source/drain isolation structure and the third source/drain isolation structure have a first configuration, the second source/drain isolation structure has a second configuration, and the second configuration is

different than the first configuration; a first epitaxial source/drain disposed over the first semiconductor layer and a second epitaxial source/drain disposed over the second semiconductor layer; and wherein in a cross-sectional view along a gate lengthwise direction: the first epitaxial source/drain extends from the first source/drain isolation structure to the second source/drain isolation structure, and the second epitaxial source/drain extends from the second source/drain isolation structure to the third source/drain isolation structure.

12. The device structure of claim 11, wherein the first source/drain isolation structure and the third source/drain isolation structure have a first width along the gate lengthwise direction, the second source/drain isolation structure has a second width along the gate lengthwise direction, and the first width is less than the second width.

13. The device structure of claim 11, further comprising: a first substrate isolation structure, a second substrate isolation structure, and a third substrate isolation structure, wherein the second substrate isolation structure is disposed between the first substrate isolation structure and the third substrate isolation structure, wherein the first source/drain isolation structure is disposed over the first substrate isolation structure, the second source/drain isolation structure is disposed over the second substrate isolation structure, and the third source/drain isolation structure is disposed over the third substrate isolation structure; wherein the first substrate isolation structure and the third substrate isolation structure have a third configuration, the second substrate isolation structure has a fourth configuration, and the third configuration is different than the fourth configuration; and wherein each of the third configuration and the fourth configuration is different than the first configuration and the second configuration.

14. The device structure of claim 13, wherein the first source/drain isolation structure and the third source/drain isolation structure have a first width along the gate lengthwise direction, the first substrate isolation structure and the third substrate isolation structure have a second width along the gate lengthwise direction, the second source/drain isolation structure and the second substrate isolation structure have a third width along the gate lengthwise direction, and the first width is less than the second width.

15. The device structure of claim 11, wherein: a first side of the first epitaxial source/drain and a first side of the second epitaxial source/drain face the second source/drain isolation structure, a second side of the first epitaxial source/drain faces the first source/drain isolation structure, and a second side of the second epitaxial source/drain faces the third source/drain isolation structure; lengths of facets of the first side of the first epitaxial source/drain are less than lengths of facets of the second side of the first epitaxial source/drain; and lengths of facets of the first side of the second epitaxial source/drain are less than lengths of facets of the second side of the second epitaxial source/drain.

16. The device structure of claim 11, wherein: a first side of the first epitaxial source/drain interfaces with the first source/drain isolation structure and a second side of the first epitaxial source/drain interfaces with the second source/drain isolation structure, wherein a length of the first side of the first epitaxial source/drain is less than a length of the second side of the first epitaxial source/drain; and a first side of the second epitaxial source/drain interfaces with the third source/drain isolation structure and a second side of the second epitaxial source/drain interfaces with the second source/drain isolation structure, wherein a length of the first side of the second epitaxial source/drain is less than a length of the second side of the second epitaxial source/drain.

17. The device structure of claim 11, further comprising a contact etch stop layer, wherein the contact etch stop layer wraps a top portion of the first source/drain isolation structure, a top portion of the second source/drain isolation structure, and a top portion of the third source/drain isolation structure.

18. A method comprising: forming a first stack of layers and a second stack of layers extending from a substrate, wherein: the first stack of layers forms a first sidewall of a first trench and a first sidewall of a second trench, the second stack of layers forms a second sidewall of the second-first

trench and a first sidewall of a third trench, and the substrate forms a bottom of the first trench, a bottom of the second trench, and a bottom of the third trench; forming a first isolation structure in a lower portion of the first trench, a second isolation structure in a lower portion of the second trench, and a third isolation structure in a lower portion of the third trench, wherein the first isolation structure, the second isolation structure, and the third isolation structure fill the lower portion of the first trench, the lower portion of the second trench, and the lower portion of the third trench, respectively; forming a sacrificial layer over the second isolation structure that partially fills an upper portion of the second trench, wherein the sacrificial layer is disposed on a side of the first stack of layers that forms the first sidewall of the second trench, a side of the second stack of layers that forms the second sidewall of the second trench, a top of the first stack of layers, and a top of the second stack of layers; forming a fourth isolation structure in an upper portion of the first trench, a fifth isolation structure in a remainder of the upper portion of the second trench, and a sixth isolation structure in an upper portion of the third trench by: forming dielectric structures that fill the upper portion of the first trench, the remainder of the upper portion of the second trench, and the upper portion of the third trench, wherein the dielectric structures include an oxygen-comprising dielectric layer wrapped by a silicon-comprising dielectric liner, and replacing top portions of the dielectric structures in the upper portions of the first trench, the second trench, and the third trench with metal-and-oxygen comprising layers; and replacing the sacrificial layer, a portion of the first stack of layers, and a portion of the second stack of layers with one or more gate layers.

19. The method of claim 18, wherein: the portion of the first stack of layers is a first portion of the first stack of layers, the portion of the second stack of layers is a first portion of the second stack of layers, and a first portion of the sacrificial layer is replaced with the one or more gate layers; and the method further includes replacing a second portion of the sacrificial layer, a second portion of the first stack of layers, and a second portion of the second stack of layers with one or more source/drain layers.

20. The method of claim 19, further comprising reducing a thickness of a portion of the metal-and-oxygen comprising layers in source/drain regions when replacing the second portion of the sacrificial layer, the second portion of the first stack of layers, and the second portion of the second stack of layers with the one or more source/drain layers.
