

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12412804

Kind Code

B2

Date of Patent

September 09, 2025

Inventor(s)

Lee; Cheng-Chin et al.

Semiconductor structure with improved heat dissipation

Abstract

A semiconductor structure is provided. The semiconductor structure includes a substrate and a device region formed over the substrate. The semiconductor structure further includes an interconnect structure formed over the device region and a first passivation layer formed over the interconnect structure. The semiconductor structure also includes a metal pad formed over and extending into the first passivation layer and a second passivation layer formed over the first passivation layer. The second passivation layer includes a thermal conductive material, and the thermal conductivity of the thermal conductive material is higher than 4 W/mK.

Inventors: Lee; Cheng-Chin (Taipei, TW), Shue; Shau-Lin (Hsinchu, TW), Lee; Shao-Kuan (Kaohsiung, TW), Chang; Hsiao-Kang (Hsinchu, TW), Tsai; Cherng-Shiaw (New Taipei, TW), Cheng; Kai-Fang (Taoyuan, TW), Huang; Hsin-Yen (New Taipei, TW), Lin; Ming-Hsien (Hsinchu County, TW), Chou; Chuan-Pu (Hsinchu County, TW), Chen; Hsin-Ping (Hsinchu County, TW), Wu; Chia-Tien (Taichung, TW), Yang; Kuang-Wei (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 87931150

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 17/693668

Filed: March 14, 2022

Prior Publication Data

Document Identifier

US 20230290705 A1

Publication Date

Sep. 14, 2023

Publication Classification

Int. Cl.: **H01L23/373** (20060101); **H01L23/522** (20060101); **H01L23/528** (20060101);
H10D30/62 (20250101); **H10D84/83** (20250101)

U.S. Cl.:

CPC **H01L23/3738** (20130101); **H01L23/3732** (20130101); **H01L23/5226** (20130101);
H01L23/5283 (20130101); **H10D30/6211** (20250101); **H10D84/834** (20250101);

Field of Classification Search

CPC: H01L (23/3738); H01L (23/3732); H01L (23/5226); H01L (23/5283); H01L (27/0886);
H01L (29/7851); H01L (21/76898); H01L (23/3677); H01L (23/481)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2014/0054761	12/2013	Lin	257/692	H01L 23/42
2019/0304900	12/2018	Chen	N/A	H01L 23/528
2020/0098683	12/2019	Shilimkar	N/A	H01L 23/5228
2022/0157690	12/2021	Lee	N/A	H01L 23/53295
2022/0310472	12/2021	Huang	N/A	H10D 30/024

Primary Examiner: Feliciano; Eliseo Ramos

Assistant Examiner: Kao; Sophia W

Attorney, Agent or Firm: McClure, Qualey & Rodack, LLP

Background/Summary

BACKGROUND

(1) Semiconductor devices are used in a variety of electronic applications, such as personal computers, cell phones, digital cameras, and other electronic equipment. Semiconductor devices are typically fabricated by sequentially depositing insulating or dielectric layers, conductive layers, and semiconductive layers of material over a semiconductor substrate, and patterning the various material layers using lithography to form circuit components and elements thereon. Many integrated circuits are typically manufactured on a single semiconductor wafer, and individual dies on the wafer are singulated by sawing between the integrated circuits along a scribe line. The individual dies are typically packaged separately, in multi-chip modules, for example, or in other types of packaging.

(2) As the semiconductor industry has progressed into nanometer technology process nodes in pursuit of higher device density, higher performance, and lower costs, challenges from both fabrication and design issues have resulted in the development of three-dimensional designs, such as the fin field effect transistor (FinFET). FinFETs are fabricated with a thin vertical “fin” (or fin

structure) extending from a substrate. The channel of the FinFET is formed in this vertical fin. A gate is provided over the fin. The advantages of a FinFET may include reducing the short channel effect and providing a higher current flow.

(3) Although existing FinFET devices and packages have generally been adequate for their intended purposes, they have not been entirely satisfactory in all respects.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It should be noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. 1A-1I are perspective views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(3) FIGS. 2A-2Q are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(4) FIG. 2R illustrates a layout of the semiconductor structure, in accordance with some embodiments of the disclosure.

(5) FIGS. 3A-3O are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(6) FIGS. 4A-4O are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(7) FIGS. 5A-5I are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(8) FIGS. 6A-6D are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

(9) FIGS. 7A-7C are cross-sectional views of a semiconductor structure, in accordance with some embodiments of the disclosure.

(10) FIGS. 8A-8G are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure.

DETAILED DESCRIPTION

(11) The following disclosure provides many different embodiments, or examples, for implementing different features of the subject matter provided. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(12) Some variations of the embodiments are described. Throughout the various views and illustrative embodiments, like reference numbers are used to designate like elements. It should be understood that additional operations can be provided before, during, and after the method, and some of the operations described can be replaced or eliminated for other embodiments of the method.

(13) Fin structures described below may be patterned by any suitable method. For example, the fin

structures may be patterned using one or more photolithography processes, including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over a substrate and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers may then be used to pattern the fin structures.

(14) Embodiments of a semiconductor structures are provided. The semiconductor structure may include a thermal conductive material having a thermal conductivity higher than 4 W/mK. In some embodiments, the isolation structure separating the gate structure into multiple regions has a relative high thermal conductivity (for example, greater than 4 W/mK), and therefore the formation of the isolation structure helps to dissipate the heat generated by the semiconductor structure. In addition, the liners and the conductive layer, or the passivation layers may also adopted the thermal conductive material for improving the thermal dissipation of the overall semiconductor structure.

(15) FIGS. 1A-1I are perspective representations of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. A substrate **102** is provided, as shown in FIG. 1A in accordance with some embodiments. The substrate **102** is a semiconductor wafer such as a silicon wafer. Alternatively or additionally, the substrate **102** includes elementary semiconductor materials, compound semiconductor materials, and/or alloy semiconductor materials. Examples of the elementary semiconductor materials include, but are not limited to, crystal silicon, polycrystalline silicon, amorphous silicon, germanium, and/or diamond. Examples of the compound semiconductor materials include, but are not limited to, silicon carbide, gallium arsenic, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide. Examples of the alloy semiconductor materials include, but are not limited to, SiGe, GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP. In some embodiments, the substrate **102** includes an epitaxial layer. For example, the substrate **102** has an epitaxial layer overlying a bulk semiconductor.

(16) Afterwards, a dielectric layer **104** and a mask layer **106** are formed over the substrate **102**, and a patterned photoresist layer **108** is formed over the mask layer **106**, as shown in FIG. 1A in accordance with some embodiments. In some embodiments, the patterned photoresist layer **108** is formed by a deposition process and a patterning process.

(17) The deposition process for forming the patterned photoresist layer **108** includes a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process. The patterning process for forming the patterned photoresist layer **108** includes a photolithography process and an etching process. The photolithography process includes photoresist coating (e.g., spin-on coating), soft baking, mask aligning, exposure, post-exposure baking, developing the photoresist, rinsing and drying (e.g., hard baking). The etching process includes a dry etching process or a wet etching process.

(18) Moreover, the dielectric layer **104** is a buffer layer between the substrate **102** and the mask layer **106**. In some embodiments, the dielectric layer **104** is used as a stop layer when the mask layer **106** is removed. In some embodiments, the dielectric layer **104** is made of silicon oxide. The mask layer **106** is made of silicon oxide, silicon nitride, silicon oxynitride, or another applicable material. In some other embodiments, more than one mask layer **106** is formed over the dielectric layer **104**.

(19) The dielectric layer **104** and the mask layer **106** is formed by deposition processes, which includes a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process.

(20) After the patterned photoresist layer **108** is formed, the dielectric layer **104** and the mask layer **106** are patterned by using the patterned photoresist layer **108** as a mask, as shown in FIG. **1B** in accordance with some embodiments. As a result, a patterned dielectric layer **105** and a patterned mask layer **107** are obtained. Afterwards, the patterned photoresist layer **108** is removed.

(21) Next, an etching process is performed on the substrate **102** to form a plurality of fin structures **110** by using the patterned dielectric layer **105** and the patterned mask layer **107** as a mask. The etching process is a dry etching process or a wet etching process.

(22) In some embodiments, the substrate **102** is etched by a dry etching process. The dry etching process includes using a fluorine-based etchant gas, such as SF₆, C₄F₈, NF₃ or a combination thereof. The etching process is a time-controlled process, and continues until the fin structures **110** reach a predetermined height. In some other embodiments, the fin structures **110** have a width that gradually increases from the top portion to the lower portion.

(23) After the fin structures **110** are formed, an insulating layer **112** is formed to cover the fin structures **110**, the patterned pad layer **105**, and the patterned mask layer **107** over the substrate **102**, as shown in FIG. **1C** in accordance with some embodiments.

(24) In some embodiments, the insulating layer **112** is made of silicon oxide, silicon nitride, silicon oxynitride, fluoride-doped silicate glass (FSG), or another low-k dielectric material. The insulating layer **112** is deposited by a chemical vapor deposition (CVD) process, a spin-on-glass process, or another applicable process.

(25) Next, the insulating layer **112** is thinned or planarized to expose the top surface of the patterned mask layer **107**. In some embodiments, the insulating layer **112** is thinned by a chemical mechanical polishing (CMP) process. Afterwards, the patterned dielectric layer **105** and the patterned mask layer **107** are removed.

(26) After the patterned dielectric layer **105** and the patterned mask layer **107** are removed, an upper portion of the insulating layer **112** is removed to form an isolation structure **114**, as shown in FIG. **1D** in accordance with some embodiments. The isolation structure **114** is a shallow trench isolation (STI) structure surrounding the fin structures **110**.

(27) In some embodiments, a portion of the fin structure **110** is embedded in the isolation structure **114**. More specifically, a lower portion of the fin structure **110** is surrounded by the isolation structure **114**, while an upper portion of the fin structure **110** protrudes from the isolation structure **114**. The isolation structure **114** is configured to prevent electrical interference or crosstalk.

(28) After the isolation structure **114** is formed, dummy gate structures **120** are formed across the fin structures **110** and extend over the isolation structure **114**, as shown in FIG. **1E** in accordance with some embodiments. In some embodiments, each of the dummy gate structures **120** includes a dummy gate dielectric layer **116** and a dummy gate electrode layer **118** formed over the dummy gate dielectric layer **116**. After the dummy gate structures **120** are formed, gate spacers **122** are formed on opposite sidewalls of each of the dummy gate structures **120**. Each of the gate spacers **122** is a single layer or multiple layers.

(29) In order to improve the speed of the FinFET device structure, the gate spacers **122** are made of low-k dielectric materials. In some embodiments, the low-k dielectric materials have a dielectric constant (k value) less than about 4. Examples of low-k dielectric materials include, but are not limited to, silicon oxide, silicon nitride, silicon carbonitride (SiCN), silicon oxide carbonitride (SiOCN), fluorinated silica glass (FSG), carbon doped silicon oxide, amorphous fluorinated carbon, parylene, bis-benzocyclobutenes (BCB), or polyimide.

(30) In some other embodiments, the gate spacers **122** are made of an extreme low-k (ELK) dielectric material with a dielectric constant (k) less than about 2.5. In some embodiments, the ELK dielectric materials include carbon doped silicon oxide, amorphous fluorinated carbon, parylene, bis-benzocyclobutenes (BCB), polytetrafluoroethylene (PTFE) (Teflon), or silicon oxycarbide polymers (SiOC). In some embodiments, ELK dielectric materials include a porous version of an existing dielectric material, such as hydrogen silsesquioxane (HSQ), porous methyl silsesquioxane

(MSQ), porous polyarylether (PAE), porous SiLK, or porous silicon oxide (SiO.sub.2).

(31) In addition, in some embodiments, the gate spacers **122** include air gaps (not shown) to further reduce their k value, such that the capacitances between the gate structures (formed subsequently) and the contacts (formed subsequently) electrically connected to the S/D structure (formed subsequently) is reduced.

(32) Afterwards, source/drain (S/D) structures **124** are formed over the fin structures **110**, as shown in FIG. **1F** in accordance with some embodiments. In some embodiments, portions of the fin structures **110** adjacent to the dummy gate structures **120** are recessed to form recesses at two sides of the fin structures **110**, and a strained material is grown in the recesses by an epitaxial (epi) process to form the S/D structures **124**. In addition, the lattice constant of the strained material may be different from the lattice constant of the substrate **102**. In some embodiments, the S/D structures **124** include Ge, SiGe, InAs, InGaAs, InSb, GaAs, GaSb, InAlP, InP, or the like.

(33) After the source/drain (S/D) structures **124** are formed, a contact etch stop layer (CESL) **126** is formed over the substrate **102**, and an inter-layer dielectric (ILD) structure **128** is formed over the CESL **126**. More specifically, the CESL **126** is formed over the S/D structures **124**, the isolation structure **114**, and the sidewalls of the gate spacers **122**. In some embodiments, the CESL **126** is made of silicon nitride, silicon oxynitride, and/or other applicable materials. Moreover, the CESL **126** is formed by plasma enhanced CVD, low-pressure CVD, atomic layer deposition (ALD), or other applicable processes.

(34) In some embodiments, the ILD structure **128** includes multilayers made of multiple dielectric materials, such as silicon oxide, silicon nitride, silicon oxynitride, phosphosilicate glass (PSG), borophosphosilicate glass (BPSG), low-k dielectric material, and/or other applicable dielectric materials. Examples of the low-k dielectric materials include, but are not limited to, fluorinated silica glass (FSG), carbon doped silicon oxide, amorphous fluorinated carbon, parylene, bis-benzocyclobutenes (BCB), or polyimide. In addition, the ILD structure **128** is formed by chemical vapor deposition (CVD), physical vapor deposition, (PVD), atomic layer deposition (ALD), spin-on coating, or another applicable process.

(35) Afterwards, a planarizing process is performed on the ILD structure **128** until the top surfaces of the dummy gate structures **120** are exposed, as shown in FIG. **1G** in accordance with some embodiments. After the planarizing process, the top surfaces of the dummy gate structures **120** is substantially level with the top surfaces of the gate spacers **122** and the ILD structure **128**. In some embodiments, the planarizing process includes a grinding process, a chemical mechanical polishing (CMP) process, an etching process, another applicable process, or a combination thereof.

(36) Next, the dummy gate structures **120** are removed to form trenches **130** in the ILD structure **128**, as shown in FIG. **1H** in accordance with some embodiments. More specifically, each of the trenches **130** is formed between each pair of the gate spacers **122**, and the fin structure **110** is exposed by the trenches **130**. The dummy gate dielectric layer **116** and the dummy gate electrode layer **118** are removed by an etching process, such as a dry etching process or a wet etching process.

(37) After the trenches **130** are formed, gate dielectric layers **132** and gate electrode layers **134** are formed in the trenches **130**, as shown in FIG. **1I** in accordance with some embodiments. More specifically, the gate electrode layers **134** are formed over the gate dielectric layers **132**, and sidewalls of the gate electrode layers **132** is covered by the gate dielectric layers **132**. In addition, work function layers (not shown) are formed between each of the gate dielectric layers **132** and each of the gate electrode layers **134**. Accordingly, a plurality of gate structures **136** are formed. Each of the gate structures **136** includes one dielectric layer **132** and one gate electrode layer **134**, and may also include work function layers (not shown) formed therebetween.

(38) Each of the gate dielectric layers **132** is a single layer or multiple layers. In some embodiments, the gate dielectric layers **132** are made of silicon oxide, silicon nitride, silicon oxynitride (SiON), dielectric material(s) with high dielectric constant (high-k), or a combination

thereof. In some embodiments, the gate dielectric layers **132** are deposited by a plasma enhanced chemical vapor deposition (PECVD) process or a spin coating process.

(39) Moreover, the gate electrode layers **134** are made of a conductive material such as aluminum (Al), copper (Cu), tungsten (W), titanium (Ti), tantalum (Ta), or another applicable material, in accordance with some embodiments. The gate electrode layers **134** are formed by a deposition process, such as a chemical vapor deposition (CVD) process, a physical vapor deposition (PVD) process, an atomic layer deposition (ALD) process, a high density plasma CVD (HDPCVD) process, a metal organic CVD (MOCVD) process, or a plasma enhanced CVD (PECVD) process.

(40) The work function layers are made of metal materials, and the metal materials include N-work-function metal or P-work-function metal. The N-work-function metal includes tungsten (W), copper (Cu), titanium (Ti), silver (Ag), aluminum (Al), titanium aluminum alloy (TiAl), titanium aluminum nitride (TiAlN), tantalum carbide (TaC), tantalum carbon nitride (TaCN), tantalum silicon nitride (TaSiN), manganese (Mn), zirconium (Zr) or a combination thereof. The P-work-function metal includes titanium nitride (TiN), tungsten nitride (WN), tantalum nitride (Ta₂N₃), ruthenium (Ru) or a combination thereof.

(41) FIGS. 2A-2Q are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. It should be noted FIGS. 2A-2Q are illustrated along the line A-A shown in FIG. 1I, but the present disclosure is not limited thereto. As shown in FIG. 2A, a dielectric layer **140** is formed on the ILD structure **128** by a deposition process. The deposition process may include a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process. For example, the dielectric layer **140** includes SiN or any other suitable dielectric material.

(42) Then, as shown in FIG. 2B, a trench **142** is formed in the dielectric layer **140** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, the trench **142** penetrates the dielectric layer **140**, the ILD structure **128** and the isolation structure **114**, and extends into a portion of the substrate **102**. In some embodiments, a bottom surface of the trench **142** is level with a top surface of the substrate **102**. In some embodiments, the trench **142** is formed between two adjacent fin structures **110**. The S/D structures **124** and the fin structures **110** are not exposed by the trench **142**.

(43) Next, as shown in FIG. 2C, an isolation material **150** is filled in the trench **142**. In some embodiments, the isolation material **150** overfills the trench **142** and therefore covers the dielectric layer **140**. For example, the isolation material **150** includes SiC, SiCN, Ga.sub.2O.sub.3, diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof. In some embodiments, the isolation material **150** is deposited by an atomic layer deposition (ALD) process, an atomic layer annealing (ALA) process, a plasma-enhanced chemical vapor deposition (PECVD) process, a physical vapor deposition (PVD) process, or any other suitable process. In some embodiments, the isolation material **150** has a thermal conductivity higher than 4 W/mK.

(44) Then, as shown in FIG. 2D, a plurality of recesses **144** are formed between another two adjacent fin structures **110** by an etching process, such as a dry etching process or a wet etching process. That is, at least one fin structure **110** is located between the recesses **144** and the isolation material **150**. The recesses **144** penetrate the dielectric layer **140**, the ILD structure **128** and the isolation structure **114**, and extend into a portion of the substrate **102**. In some embodiments, a bottom surface of the recesses **144** is level with a top surface of the substrate **102**.

(45) In some embodiments, as shown in FIG. 2E, liners **145** are formed on the isolation material **150** by a deposition process, such as a chemical vapor deposition (CVD) process, an atomic layer deposition (ALD) process, or another applicable process. The liners **145** are also deposited in the recesses **144**. In some embodiments, the liners **145** are conformally formed on the isolation material **150** and sidewalls and a bottom surface of each of the recesses **144**. For example, the liners **145** include SiN or any other suitable dielectric material. Next, as shown in FIG. 2F, a

sacrificial material **147** overfills the recesses **144** and therefore covers the liners **145**. For example, the sacrificial material **147** includes an oxide material or any other suitable material.

(46) In some embodiments, as shown in FIG. 2G, a planarization process is performed on the sacrificial material **147**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, an isolation structure **152** is formed, and a sacrificial layer **148** is formed within the liners **145**. In some embodiments, a top surface of the sacrificial layer **148** is substantially level with a top surface of the liners **145** and a top surface of the isolation structure **152**. Next, as shown in FIG. 2H, the sacrificial layer **148** is removed by an etching process, such as a dry etching process or a wet etching process. A plurality of recesses **149** are formed for subsequent deposition process.

(47) In some embodiments, as shown in FIG. 2I, a barrier layer **158** is deposited on the ILD structure **128** and in the recesses **149**, and a conductive material **160** is formed over the barrier layer **158**. For example, the barrier layer **158** is made of tantalum (Ta), tantalum nitride (TaN), titanium (Ti), titanium nitride (TiN), cobalt tungsten (CoW) or another applicable material. In some embodiments, the barrier layer **158** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process. In some embodiments, the second conductive material **160** is made of tungsten (W), cobalt (Co), titanium (Ti), aluminum (Al), copper (Cu), tantalum (Ta), platinum (Pt), molybdenum (Mo), silver (Ag), manganese (Mn), zirconium (Zr), ruthenium (Ru), or another application material. In some embodiments, the conductive material **160** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process.

(48) Then, as shown in FIG. 2J, a planarization process is performed on the conductive material **160**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, a plurality of conductive vias **162** are formed. In some embodiments, as shown in FIG. 2K, a plurality of passivation layers **163** and **164** are successively formed over the isolation structure **152** and the conductive vias **162**. Next, as shown in FIG. 2L, a plurality of trenches **165** are formed in the passivation layers **163** and **164** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, an adhesive layer **166** is formed on the bottom of the trenches **165** and over the S/D structures **124**. The adhesive layer **166** is exposed from the trenches **165**. For example, the adhesive layer **166** includes silicide or any other suitable material.

(49) In some embodiments, as shown in FIG. 2M, a seed layer **170** is formed on the passivation layer **164** and on sidewalls and a bottom surface of the trenches **165**, a conductive material **172** is formed on the seed layer **170**. In some embodiments, the seed layer **170** is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer **170** includes a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. In some embodiments, the conductive material **172** includes Cu, CuAl, Al, or any other suitable material. The conductive material **172** may be formed by plating, such as electroplating or electroless plating, or the like.

(50) Then, as shown in FIG. 2N, a planarization process is performed on the conductive material **172**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process, after the planarization process is completed, a conductive structure **173** is formed. In some embodiments, as shown in FIG. 2O, the overall semiconductor structure is flipped, and a plurality of trenches **175** are formed in the substrate **102**. In some embodiments, before forming the trenches **175**, the substrate **102** is

thinned. For example, the substrate **102** is thinned by a CMP process or any other suitable process, and a remaining thickness of the thinned substrate **102** is in a range from about 50 μm to about 200 μm . The trenches **175** expose the conductive vias **162**. Next, as shown in FIG. 2P, a conductive structure **176** is formed in the trenches **175**. In some embodiments, the conductive structure **176** includes Cu, CuAl, Al, or any other suitable material. It is noted that the conductive structure **176** may be formed by the similar processes as forming the conductive structure **173**. After that, as shown in FIG. 2Q, the overall semiconductor structure is flipped for performing subsequent processes.

(51) FIG. 2R illustrates a layout of the semiconductor structure, in accordance with some embodiments of the disclosure. As shown in FIG. 2R, the gate structure **136** is formed across the fin structures **110**. The isolation structure **152** separates the gate structure **136** into a first region **136A** and a second region **136B**. In some embodiments, the isolation structure **152** and the conductive structure **173** is partially overlapped with each other in a vertical direction. Since the isolation structure **152** has a relative high thermal conductivity (for example, greater than 4), the formation of the isolation structure **152** helps to dissipate the heat generated by the semiconductor structure.

(52) FIGS. 3A-3O are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. It should be noted FIGS. 3A-3O are illustrated along the line A-A shown in FIG. 1I, but the present disclosure is not limited thereto. As shown in FIG. 3A, a dielectric layer **140** is formed on the ILD structure **128** by a deposition process. The deposition process may include a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process. For example, the dielectric layer **140** includes SiN or any other suitable dielectric material.

(53) Then, as shown in FIG. 3B, a trench **142** and a plurality of recesses **144** are formed in the dielectric layer **140** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, the trench **142** and the recesses **144** penetrate the dielectric layer **140**, the ILD structure **128** and the isolation structure **114**, and extend into a portion of the substrate **102**. In some embodiments, bottom surfaces of the trench **142** and the recesses **144** are level with a top surface of the substrate **102**. In some embodiments, the trench **142** is formed between two adjacent fin structures **110**, and the recesses **144** are formed between another two adjacent fin structures **110**. That is, at least one fin structure **110** is located between one of the recesses **144** and the trench **142**. In some embodiments, the S/D structures **124** and the fin structures **110** may not be exposed by the trench **142**.

(54) Next, as shown in FIG. 3C, an isolation material **150** is filled in the trench **142** and the recesses **144**. In some embodiments, the isolation material **150** overfills the trench **142** and is conformally formed on sidewalls and a bottom surface of each of the recesses **144**. For example, the isolation material **150** includes SiC, SiCN, Ga.sub.2O.sub.3, diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof. In some embodiments, the isolation material **150** is deposited by an atomic layer deposition (ALD) process, an atomic layer annealing (ALA) process, a plasma-enhanced chemical vapor deposition (PECVD) process, a physical vapor deposition (PVD) process, or any other suitable process. In some embodiments, the isolation material **150** has a thermal conductivity higher than 4 W/mK.

(55) Then, as shown in FIG. 3D, a sacrificial material **147** overfills the recesses **144** and therefore covers the isolation material **150**. For example, the sacrificial material **147** includes an oxide material or any other suitable material. In some embodiments, as shown in FIG. 3E, a planarization process is performed on the sacrificial material **147**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, an isolation structure **152** is formed in the trench **142**, and a sacrificial layer **148** and liners **153** are formed in the recesses **144**. It is

noted that the isolation structure **152** and the liners **153** are made of the same material. In some embodiments, a top surface of the sacrificial layer **148** is substantially level with a top surface of the liners **153** and a top surface of the isolation structure **152**.

(56) Next, as shown in FIG. 3F, the sacrificial layer **148** is removed by an etching process, such as a dry etching process or a wet etching process. A plurality of recesses **149** are formed for subsequent deposition process. In some embodiments, as shown in FIG. 3G, a barrier layer **158** is deposited on the ILD structure **128** and in the recesses **149**, and a conductive material **160** is formed over the barrier layer **158**. For example, the barrier layer **158** is made of tantalum (Ta), tantalum nitride (Ta_N), titanium (Ti), titanium nitride (Ti_N), cobalt tungsten (CoW) or another applicable material. In some embodiments, the barrier layer **158** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process. In some embodiments, the second conductive material **160** is made of tungsten (W), cobalt (Co), titanium (Ti), aluminum (Al), copper (Cu), tantalum (Ta), platinum (Pt), molybdenum (Mo), silver (Ag), manganese (Mn), zirconium (Zr), ruthenium (Ru), or another application material. In some embodiments, the conductive material **160** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process.

(57) Then, as shown in FIG. 3H, a planarization process is performed on the conductive material **160**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, a plurality of conductive vias **162** are formed. It is noted that since the liners **153** that is adjacent to the conductive vias **162** has a thermal conductivity higher than 4 W/mK, the thermal dissipation of the overall semiconductor structure may be improved.

(58) In some embodiments, as shown in FIG. 3I, a plurality of passivation layers **163** and **164** are successively formed over the isolation structure **152** and the conductive vias **162**. Next, as shown in FIG. 3J, a plurality of trenches **165** are formed in the passivation layers **163** and **164** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, an adhesive layer **166** is formed on the bottom of the trenches **165** and over the S/D structures **124**. The adhesive layer **166** is exposed from the trenches **165**. For example, the adhesive layer **166** includes silicide or any other suitable material.

(59) In some embodiments, as shown in FIG. 3K, a seed layer **170** is formed on the passivation layer **164** and on sidewalls and a bottom surface of the trenches **165**, a conductive material **172** is formed on the seed layer **170**. In some embodiments, the seed layer **170** is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer **170** includes a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. In some embodiments, the conductive material **172** includes Cu, CuAl, Al, or any other suitable material. The conductive material **172** may be formed by plating, such as electroplating or electroless plating, or the like.

(60) Then, as shown in FIG. 3L, a planarization process is performed on the conductive material **172**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process, after the planarization process is completed, a conductive structure **173** is formed. In some embodiments, as shown in FIG. 3M, the overall semiconductor structure is flipped, and a plurality of trenches **175** are formed in the substrate **102**. In some embodiments, before forming the trenches **175**, the substrate **102** is thinned. For example, the substrate **102** is thinned by a CMP process or any other suitable process, and a remaining thickness of the thinned substrate **102** is in a range from about 50 μm to about 200 μm . The trenches **175** expose the conductive vias **162**. Next, as shown in FIG. 3R, a conductive structure **176** is formed in the trenches **175**. In some embodiments, the conductive structure **176**

includes Cu, CuAl, Al, or any other suitable material. It is noted that the conductive structure **176** may be formed by the similar processes as forming the conductive structure **173**. After that, as shown in FIG. **30**, the overall semiconductor structure is flipped for performing subsequent processes.

(61) FIGS. **4A-4O** are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. It should be noted FIGS. **4A-4O** are illustrated along the line A-A shown in FIG. **1I**, but the present disclosure is not limited thereto. As shown in FIG. **4A**, a dielectric layer **140** is formed on the ILD structure **128** by a deposition process. The deposition process may include a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process. For example, the dielectric layer **140** includes SiN or any other suitable dielectric material.

(62) Then, as shown in FIG. **4B**, a trench **142** and a plurality of recesses **144** are formed in the dielectric layer **140** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, the trench **142** and the recesses **144** penetrate the dielectric layer **140**, the ILD structure **128** and the isolation structure **114**, and extend into a portion of the substrate **102**. In some embodiments, bottom surfaces of the trench **142** and the recesses **144** are level with a top surface of the substrate **102**. In some embodiments, the trench **142** is formed between two adjacent fin structures **110**, and the recesses **144** are formed between another two adjacent fin structures **110**. That is, at least one fin structure **110** is located between one of the recesses **144** and the trench **142**. In some embodiments, the S/D structures **124** and the fin structures **110** may not be exposed by the trench **142**.

(63) Next, as shown in FIG. **4C**, an isolation material **150** and an electrical dielectric material **151** are filled in the trench **142** and the recesses **144**. In some embodiments, the isolation material **150** and the electrical dielectric material **151** overfill the trench **142** and are conformally formed on sidewalls and a bottom surface of each of the recesses **144**. For example, the isolation material **150** includes SiC, SiCN, GA.sub.2O.sub.3, diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof. In some embodiments, the isolation material **150** is deposited by an atomic layer deposition (ALD) process, an atomic layer annealing (ALA) process, a plasma-enhanced chemical vapor deposition (PECVD) process, a physical vapor deposition (PVD) process, or any other suitable process. In some embodiments, the isolation material **150** has a thermal conductivity higher than 4 W/mK.

(64) Then, as shown in FIG. **4D**, a sacrificial material **147** overfills the recesses **144** and therefore covers the isolation material **150** and the electrical dielectric material **151**. For example, the sacrificial material **147** includes an oxide material or any other suitable material. In some embodiments, as shown in FIG. **4E**, a planarization process is performed on the sacrificial material **147**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, an isolation structure **152** is formed in the trench **142**, a sacrificial layer **148**, liners **153**, and an electrical dielectric layer **154** are formed in the recesses **144**. In particular, the electrical dielectric layer **154** is located between the liners **153** and the sacrificial layer **148**. It is noted that the isolation structure **152** and the liners **153** are made of the same material. In some embodiments, a top surface of the sacrificial layer **148** is substantially level with a top surface of the liners **153** and a top surface of the isolation structure **152**.

(65) Next, as shown in FIG. **4F**, the sacrificial layer **148** is removed by an etching process, such as a dry etching process or a wet etching process. A plurality of recesses **149** are formed and expose the electrical dielectric layer **154** for subsequent deposition process. In some embodiments, as shown in FIG. **4G**, a barrier layer **158** is deposited on the ILD structure **128** and in the recesses **149**, and a conductive material **160** is formed over the barrier layer **158**. For example, the barrier layer **158** is made of tantalum (Ta), tantalum nitride (TaN), titanium (Ti), titanium nitride (TiN),

cobalt tungsten (CoW) or another applicable material. In some embodiments, the barrier layer **158** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process. In some embodiments, the second conductive material **160** is made of tungsten (W), cobalt (Co), titanium (Ti), aluminum (Al), copper (Cu), tantalum (Ta), platinum (Pt), molybdenum (Mo), silver (Ag), manganese (Mn), zirconium (Zr), ruthenium (Ru), or another application material. In some embodiments, the conductive material **160** is formed by a deposition process, such as a chemical vapor deposition (CVD) process, physical vapor deposition (PVD) process, atomic layer deposition (ALD) process, plating process or another application process. (66) Then, as shown in FIG. 4H, a planarization process is performed on the conductive material **160**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, a plurality of conductive vias **162** are formed. It is noted that since the electrical dielectric layer **154** is located between the liners **153** and the conductive vias **162**, the possibility that a breakdown occurred between the liners **153** and the conductive vias **162** may be reduced.

(67) In some embodiments, as shown in FIG. 4I, a plurality of passivation layers **163** and **164** are successively formed over the isolation structure **152** and the conductive vias **162**. Next, as shown in FIG. 4J, a plurality of trenches **165** are formed in the passivation layers **163** and **164** by an etching process, such as a dry etching process or a wet etching process. In some embodiments, an adhesive layer **166** is formed on the bottom of the trenches **165** and over the S/D structures **124**. The adhesive layer **166** is exposed from the trenches **165**. For example, the adhesive layer **166** includes silicide or any other suitable material.

(68) In some embodiments, as shown in FIG. 4K, a seed layer **170** is formed on the passivation layer **164** and on sidewalls and a bottom surface of the trenches **165**, a conductive material **172** is formed on the seed layer **170**. In some embodiments, the seed layer **170** is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer **170** includes a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. In some embodiments, the conductive material **172** includes Cu, CuAl, Al, or any other suitable material. The conductive material **172** may be formed by plating, such as electroplating or electroless plating, or the like.

(69) Then, as shown in FIG. 4L, a planarization process is performed on the conductive material **172**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process, after the planarization process is completed, a conductive structure **173** is formed. In some embodiments, as shown in FIG. 4M, the overall semiconductor structure is flipped, and a plurality of trenches **175** are formed in the substrate **102**. In some embodiments, before forming the trenches **175**, the substrate **102** is thinned. For example, the substrate **102** is thinned by a CMP process or any other suitable process, and a remaining thickness of the thinned substrate **102** is in a range from about 50 μm to about 200 μm . The trenches **175** expose the conductive vias **162**. Next, as shown in FIG. 4R, a conductive structure **176** is formed in the trenches **175**. In some embodiments, the conductive structure **176** includes Cu, CuAl, Al, or any other suitable material. It is noted that the conductive structure **176** may be formed by the similar processes as forming the conductive structure **173**. After that, as shown in FIG. 40, the overall semiconductor structure is flipped for performing subsequent processes.

(70) FIGS. 5A-5I are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. As shown in FIG. 5A, a substrate **200** is provided. The device region **210** is formed on the substrate **200**. In addition, an etch stop layer **215** is formed on the device region **210**. In some embodiments, the substrate **200** includes a conductive

structure **50** and a conductive via **52** electrically connected to the conductive structure **50**. It is noted that the conductive structure **50** and the conductive via **52** are illustrative, and the present disclosure is not limited thereto. For example, the conductive structure **50** and the conductive via **52** are the conductive structures and the conductive vias discussed in the previous embodiments. (71) In addition, the device region **210** includes a plurality of devices **60** and a plurality of conductive vias **62** electrically connected to the devices **60**. For example, the devices **60** are transistors, such as planar field effect transistors (FETs), FinFETs, nanostructure transistors, or other suitable transistors. The nanostructure transistors may include nanosheet transistors, nanowire transistors, gate-all-around (GAA) transistors, multi-bridge channel (MBC) transistors, or any transistors having the gate electrode surrounding the channels. In some embodiments, one of the devices includes a gate structure **64** and spacers **66** that are disposed adjacent to the gate structure **64**.

(72) A conductive material **220** is formed on the etch stop layer **215** and includes a two-dimensional (2D) material. The term “2D material” used in this disclosure refers to single layer material or monolayer-type material that is atomically thin crystalline solid having intralayer covalent bonding and interlayer van der Waals bonding. Examples of a 2D material may include graphene, hexagonal boron nitride (h-BN), or transition metal dichalcogenides (MX₂), where M is a transition metal element and X is a chalcogenide element. Some exemplary MX₂ materials may include, but are not limited to, MoS₂, TiS₂, MoSe₂, or any combination thereof, which has anisotropic conductivity. In some embodiments, the conductive material **220** has a relative high horizontal conductivity and relative low vertical conductivity. In some embodiments, the conductive material **220** has Al₂O₃, AlN, diamond, C₃N₄, h-BN, graphite, graphene, Si₃N₄, or a combination thereof.

(73) A dielectric layer **224** and a mask layer **226** are formed over the conductive material **220**, and a patterned photoresist layer **228** is formed over the mask layer **226**, as shown in FIG. 5B in accordance with some embodiments. In some embodiments, the patterned photoresist layer **228** is formed by a deposition process and a patterning process.

(74) The deposition process for forming the patterned photoresist layer **228** includes a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process. The patterning process for forming the patterned photoresist layer **108** includes a photolithography process and an etching process. The photolithography process includes photoresist coating (e.g., spin-on coating), soft baking, mask aligning, exposure, post-exposure baking, developing the photoresist, rinsing and drying (e.g., hard baking). The etching process includes a dry etching process or a wet etching process.

(75) Moreover, the dielectric layer **224** is a buffer layer between the conductive material **220** and the mask layer **226**. In some embodiments, the dielectric layer **224** is used as a stop layer when the mask layer **226** is removed. In some embodiments, the dielectric layer **224** is made of silicon oxide. The mask layer **226** is made of silicon oxide, silicon nitride, silicon oxynitride, or another applicable material. In some other embodiments, more than one mask layer **226** is formed over the dielectric layer **224**. The dielectric layer **224** and the mask layer **226** is formed by deposition processes, which includes a chemical vapor deposition (CVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, a sputtering process, or another applicable process.

(76) Next, as shown in FIG. 5C, a conductive layer **221** is formed by an etching process, such as a dry etching process or a wet etching process, and a plurality of recesses **222** is formed in the conductive layer **221**. It is noted that the conductive layer **221** is shown as several separate sections, these sections may be electrically connected to each other. In some embodiments, as shown in FIG. 5D, a dielectric material **230** overfills the recesses **222** and therefore covers the conductive layer **221**. For example, the dielectric material **230** has a dielectric constant (k-value) in a range from

about 3.1 to about 4.5. The density of the dielectric material **230** may be higher than 1.2 g/cm.³, such as in a range from about 1.3 g/cm.³ to about 2.5 g/cm.³. In some embodiments, the Young's modulus of the dielectric material **230** is greater than about 10 GPa. The above parameters may help to reduce the possibility that the conductive layer **221** is damaged during the deposition of the dielectric material **230**.

(77) In some embodiments, as shown in FIG. 5E, a planarization process is performed on the dielectric material **230**. For example, the planarization process may be a grinding process, a chemical mechanical polish (CMP) process, an etching process or any other suitable process. After the planarization process is completed, a dielectric layer **232** is formed in the recesses **222**.

(78) Then, as shown in FIG. 5F, an etch stop layer **235** is formed on the conductive layer **221** and the dielectric layer **232**. That is, the conductive layer **221** and the dielectric layer **232** are located between the etch stop layer **215** and the etch stop layer **235**. In some embodiments, as shown in FIG. 5G in accordance with some embodiments, a dielectric layer **240** is deposited over the etch stop layer **215**. Similarly, a dielectric layer **244** and a mask layer **246** are formed over the dielectric layer **240**, and a patterned photoresist layer **248** is formed over the mask layer **246**. In some embodiments, the patterned photoresist layer **228** is formed by a deposition process and a patterning process.

(79) Then, as shown in FIG. 5H, a recess **242** is formed by an etching process, such as a dry etching process or a wet etching process. In some embodiment, the recess **242** penetrates the dielectric layer **240** and the etch stop layer **235**, and exposes at least a portion of the conductive layer **221**. In some embodiment, as shown in FIG. 5H, a conductive via **250** is formed in the recess **242** and electrically/physically connected to the conductive layer **221**.

(80) FIGS. 6A-6D are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. It is noted that the processes shown in FIGS. 6A-6D may continue on the process shown in FIG. 5E, and therefore the processes shown in FIGS. 5A-5E are also included in the present embodiment. In some embodiments, the conductive layer **221** is recessed to be lower than the dielectric layer **232** by an additional etching process, such as a dry etching process or a wet etching process. Then, as shown in FIG. 6A, an etch stop layer **235** is formed on the conductive layer **221** and the dielectric layer **232**. In some embodiments, the etch stop layer **235** is conformally formed on the conductive layer **221** and the dielectric layer **232**.

(81) In some embodiments, as shown in FIG. 6B in accordance with some embodiments, a dielectric layer **240** is deposited over the etch stop layer **215**. Similarly, a dielectric layer **244** and a mask layer **246** are formed over the dielectric layer **240**, and a patterned photoresist layer **248** is formed over the mask layer **246**. In some embodiments, the patterned photoresist layer **228** is formed by a deposition process and a patterning process.

(82) Then, as shown in FIG. 6C, a recess **242** is formed by an etching process, such as a dry etching process or a wet etching process. In some embodiment, the recess **242** penetrates the dielectric layer **240** and the etch stop layer **235**, and exposes at least a portion of the conductive layer **221**. In some embodiment, as shown in FIG. 6D, a conductive via **250** is formed in the recess **242** and electrically/physically connected to the conductive layer **221**. It is noted that the recess **242** and the conductive via **250** formed therein are aligned to the portion of the conductive layer **221** more successfully since the height difference exists between the conductive layer **221** and the dielectric layer **232**. Therefore, the possibility of the misalignment between conductive via **250** and the conductive layer **221** may be reduced.

(83) FIGS. 7A-7C are cross-sectional views of a semiconductor structure, in accordance with some embodiments of the disclosure. It is noted that the semiconductor structures shown in FIGS. 7A-7C include a substrate **200**, a device region **210** formed on the substrate **200**, an interconnect structure **260** formed on and electrically connected to the device region **210**, and a heat sink **270** disposed on the interconnect structure **260**. The interconnect structure **260** are formed by repeating the

processes shown in FIGS. 5A-5I and/or FIGS. 6A-6D, and therefore includes multiple layers of the conductive layer **221**, the dielectric layers **232**, **240** and the conductive via **250**. The heat sink **270** is configured to dissipate the heat generated by the overall semiconductor structure.

(84) In some embodiments, as shown in FIG. 7B, the overall semiconductor structure is flipped, and a through via **280** is formed adjacent to the conductive layers **221** and the conductive vias **250**, penetrating the substrate **200**, the device region **210**, and the dielectric layers **240**. In some embodiments, the through via **280** is in contact with the heat sink **270**. For example, the through via **280** is formed by laser drilling process and metal filling process. However, any other suitable process may also be adopted. The through via **280** is made of metallic material or any other suitable thermal-conductive material. Accordingly, the heat dissipation of the overall semiconductor structure is improved, especially in a vertical direction.

(85) In some embodiments, as shown in FIG. 7C, the overall semiconductor structure is flipped, and a through via **285** is formed adjacent to the conductive layers **221** and the conductive vias **250**, penetrating the substrate **200**, the device region **210**, the dielectric layers **240**, and the heat sink **270**. In some embodiments, the through via **285** is electrically connected to external components and configured to transmit power to the substrate **200** and the device region **210**. For example, the through via **285** is made of metallic material or any other suitable thermal-conductive material. Accordingly, the heat dissipation of the overall semiconductor structure is improved, and the variety of circuit design of the overall semiconductor structure may be enhanced.

(86) FIGS. 8A-8G are cross-sectional views of various stages of forming a semiconductor structure, in accordance with some embodiments of the disclosure. It is noted that the semiconductor structures shown in FIGS. 8A-8G include a substrate **300**, a device region **310** formed on the substrate **300**, an interconnect structure **320** formed on and electrically connected to the device region **310**. In some embodiments, the interconnect structure **320** are formed by repeating the processes shown in FIGS. 5A-5I and/or FIGS. 6A-6D. In some embodiments, the interconnect structure **320** includes a dielectric layer **321** and a conductive layer **322** formed in the dielectric layer **321**. It is noted that the conductive layer **322** is shown as several separate sections, these sections may be electrically connected to each other.

(87) Next, as shown in FIG. 8B, a first passivation layer **330** is formed over the interconnect structure **320**. In some embodiments, the first passivation layer **330** includes a first layer **331** in contact with the interconnect structure **320** and a second layer **332** formed on the first layer **331**. In some embodiments, the first layer **331** and the second layer **332** are made of undoped silicate glass (USG), SiN, or any other suitable material. For example, the first layer **331** and the second layer **332** are deposited by a high density plasma CVD (HDPCVD) process, or a plasma enhanced CVD (PECVD) process. However, any other deposition process may also be adopted.

(88) Then, as shown in FIG. 8C, a recess **333** is formed by an etching process, such as a dry etching process or a wet etching process. In some embodiment, the recess **333** penetrates the first passivation layer **330**, and exposes at least a portion of the conductive layer **322**. In some embodiments, as shown in FIG. 8D, a barrier layer **341**, a metal pad **342**, and an anti-reflection layer **343** are formed over and extending into the first passivation layer **330**. In some embodiments, the barrier layer **341**, the metal pad **342**, and the anti-reflection layer **343** are successively deposited. That is, the barrier layer **341** is located between the metal pad **342** and the first passivation layer **330**. The barrier layer **341** includes Ta, TiN, TaN and may be deposited by PVD, ALD, CVD, or a combination thereof. In some embodiments, the metal pad **342** includes Cu, CuAl, or Al. In some embodiments, the anti-reflection layer **343** includes SiON and may be deposited by PVD, ALD, CVD, or a combination thereof. Then, as shown in FIG. 8E, the barrier layer **341**, the metal pad **342**, and the anti-reflection layer **343** are patterned for subsequent process.

(89) In some embodiments, as shown in FIG. 8F, a second passivation layer **350** is formed over the first passivation layer **330**. In some embodiments, the anti-reflection layer **343** is located between the metal pad **342** and the second passivation layer **350**. In some embodiments, the second

passivation layer **350** is in direct contact with the barrier layer **341** and the anti-reflection layer **343**. The second passivation layer **350** includes a first layer **351** formed over the metal pad **342** and a second layer **352** formed on the first layer **351**. In some embodiments, the first layer **351** includes a thermal conductive material, and the thermal conductivity of the thermal conductive material is higher than 4 W/mK. For example, the thermal conductive material includes SiC, SiCN, GA.sub.2O.sub.3, diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof, and may be deposited by an atomic layer deposition (ALD) process, an atomic layer annealing (ALA) process, a plasma-enhanced chemical vapor deposition (PECVD) process, a physical vapor deposition (PVD) process, or any other suitable process. In some embodiments, the first layer **351** and the second layer **352** are made of different materials. For example, the second layer **352** is made of undoped silicate glass (USG), SiN, or any other suitable material. For example, the second layer **352** is deposited by a high density plasma CVD (HDPCVD) process, or a plasma enhanced CVD (PECVD) process. However, any other deposition process may also be adopted. Since the first layer **351** is made of a thermal conductive material, the heat generated by the overall semiconductor structure may be conducted along the metal pad **342** and the first layer **351**, indicated as the arrows in FIG. **8F**. Accordingly, the thermal dissipation of the overall semiconductor structure may be improved, enhancing the performance of the overall semiconductor structure.

(90) Alternatively, in some embodiments, as shown in FIG. **8G**, the first passivation layer **330** includes the above thermal conductive material. For example, the second layer **332** is made of a thermal conductive material. The material and formation of the second layer **332** may be the same as the first layer **351**, which is discussed above. Since the second layer **332** and the first layer **351** are both made of a thermal conductive material, the heat generated by the overall semiconductor structure may be conducted along the second layer **332** and the first layer **351**, indicated as the arrows in FIG. **8G**. Accordingly, the thermal dissipation region is greater, enhancing the performance of the overall semiconductor structure.

(91) Embodiments of a semiconductor structures are provided. The semiconductor structure may include a thermal conductive material having a thermal conductivity higher than 4 W/mK. In some embodiments, the isolation structure separating the gate structure, the liners and the conductive layer, or the passivation layers may also adopted the thermal conductive material for improving the thermal dissipation of the overall semiconductor structure. In some embodiments, an electrical dielectric layer is formed between the liners and the conductive vias for reducing the possibility that a breakdown occurred between the liners and the conductive vias. In some embodiments, a through via is formed penetrating the substrate and the interconnect structure for improving the heat dissipation of the overall semiconductor structure, especially in a vertical direction.

(92) In some embodiments, a semiconductor structure is provided. The semiconductor structure includes a substrate and a device region formed over the substrate. The semiconductor structure also includes an interconnect structure formed over the device region and a first passivation layer formed over the interconnect structure. The semiconductor structure further includes a metal pad formed over and extending into the first passivation layer and a second passivation layer formed over the first passivation layer. The second passivation layer comprises a thermal conductive material, and a thermal conductivity of the thermal conductive material is higher than 4 W/mK.

(93) In some embodiments, a semiconductor structure is provided. The semiconductor structure includes a substrate, and a first fin, a second fin, and a third fin that protrude from the substrate. The semiconductor structure also includes a gate structure formed across the first fin, the second fin, and the third fin. The semiconductor structure includes a first source/drain structure attached to the first fin, a second source/drain structure attached to the second fin, a third source/drain structure attached to the third fin. The semiconductor structure further includes a conductive via disposed between the first source/drain structure and the second source/drain structure and an isolation structure disposed between the second source/drain structure and the third source/drain structure.

The isolation structure separates the gate structure into a first region and a second region and comprises a thermal conductive material having a thermal conductivity higher than 4 W/mK. (94) In some embodiments, a semiconductor structure is provided. The semiconductor structure includes a substrate and a device region formed over the substrate. The semiconductor structure also includes a dielectric layer formed over the device region and a conductive layer formed in the dielectric layer. The conductive layer has anisotropic conductivity. The semiconductor structure further includes a conductive via formed in the dielectric layer and connected to the conductive layer.

(95) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor structure, comprising: a substrate; a device region formed over the substrate; an interconnect structure formed over the device region; a first passivation layer formed over the interconnect structure; a metal pad formed over and extending into the first passivation layer; a second passivation layer formed over the first passivation layer, wherein the second passivation layer comprises a thermal conductive material, and a thermal conductivity of the thermal conductive material is higher than 4 W/mK; a barrier layer between the metal pad and the first passivation layer; and an anti-reflection layer between the metal pad and the second passivation layer.
2. The semiconductor structure as claimed in claim 1, wherein the second passivation layer comprises: a first layer formed over the metal pad; and a second layer, formed over the first layer, wherein the first layer and the second layer are made of different materials.
3. The semiconductor structure as claimed in claim 2, wherein the first layer is made of the thermal conductive material.
4. The semiconductor structure as claimed in claim 1, wherein the first passivation layer comprises the thermal conductive material.
5. The semiconductor structure as claimed in claim 1, wherein the second passivation layer is in direct contact with the barrier layer and the anti-reflection layer.
6. The semiconductor structure as claimed in claim 1, wherein the thermal conductive material comprises SiC, SiCN, Ga.sub.2O.sub.3, diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof.
7. The semiconductor structure as claimed in claim 1, wherein the barrier layer comprises Ta, TiN, or TaN.
8. A semiconductor structure, comprising: an interconnect structure formed over a substrate and comprising: a dielectric layer; and a conductive layer formed in and partially exposed from the dielectric layer; a first passivation layer formed over the interconnect structure; a metal pad formed over the first passivation layer and electrically connected to the conductive layer, wherein the metal pad penetrates the first passivation layer and in contact with the conductive layer; a barrier layer laterally sandwiched between the metal pad and the first passivation layer; and a second passivation layer formed over the first passivation layer and the metal pad, wherein the second passivation layer comprises: a first layer covering the metal pad; and a second layer on the first layer, wherein the first layer and the second layer are made of different materials.

9. The semiconductor structure as claimed in claim 8, wherein the second layer is spaced apart from the metal pad via the first layer.
 10. The semiconductor structure as claimed in claim 8, further comprising an anti-reflection layer between the metal pad and the first layer.
 11. The semiconductor structure as claimed in claim 10, wherein in a direction perpendicular to a normal direction of the substrate, a width of the anti-reflection layer is substantially equal to a width of the metal pad.
 12. The semiconductor structure as claimed in claim 10, wherein the anti-reflection layer comprises SiON.
 13. The semiconductor structure as claimed in claim 8, wherein the barrier layer comprises Ta, TiN, or TaN.
 14. The semiconductor structure as claimed in claim 8, wherein the first layer comprises a thermal conductive material, and a thermal conductivity of the thermal conductive material is higher than 4 W/mK.
 15. The semiconductor structure as claimed in claim 8, wherein the first layer comprises SiC, SiCN, Ga_2O_3 , diamond, h-BN, p-BN, a-BN, single crystal AlN, p-AlN, or a combination thereof.
 16. A method for fabricating a semiconductor structure, comprising: forming an interconnect structure over a substrate; forming a first passivation layer over the interconnect structure; forming a metal pad over the first passivation layer, wherein the metal pad passes through the first passivation layer and is electrically connected to the interconnect structure; and forming a second passivation layer over the metal pad, wherein the second passivation layer comprises a thermal conductive material over a top surface and sidewalls of the metal pad, and a thermal conductivity of the thermal conductive material is higher than 4 W/mK.
 17. The method as claimed in claim 16, further comprising: forming a recess penetrating the first passivation layer and partially exposing a conductive layer of the interconnect structure.
 18. The method as claimed in claim 17, further comprising: filling a barrier layer and the metal pad into the recess on the first passivation layer.
 19. The method as claimed in claim 16, wherein forming the first passivation layer further comprises forming the thermal conductive material over the interconnect structure, and the thermal conductive materials in the first passivation layer and the second passivation layer are in contact with each other.
 20. The method as claimed in claim 16, wherein forming the second passivation layer further comprises forming a passivation material over the thermal conductive material, and the passivation material comprises undoped silicate glass (USG) or SiN.
-