

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12402521
B2
August 26, 2025
Zeng; Kewen et al.

Display substrate and manufacturing method therefor, and display device

Abstract

A display substrate and a manufacturing method therefor, and a display device. The display substrate comprises a stretchable area, the stretchable area comprises multiple pixel island areas spaced apart from each other, multiple hole areas, and connection bridge areas located between the pixel island areas and the hole areas; each of the hole areas is provided with one or more openings, and comprises a composite structural layer stacked on the substrate, each of the openings penetrates through the composite structural layer and a part of the opening is provided in the substrate, the opening penetrates through or does not penetrate through the substrate, and the wall of the opening is provided with separation grooves; and each of the hole areas further comprises a functional film layer provided on the composite structural layer and on the wall of each opening, and the functional film layer is separated at the separation grooves.

Inventors:	Zeng; Kewen (Beijing, CN), Chan; Yucheng (Beijing, CN), He; Xiangfei (Beijing, CN), Jia; Li (Beijing, CN), Chen; Teng (Beijing, CN), Chen; Gong (Beijing, CN), Yang; Bo (Beijing, CN)
Applicant:	Chengdu BOE Optoelectronics Technology Co., Ltd. (Sichuan, CN); BOE Technology Group Co., Ltd. (Beijing, CN)
Family ID:	1000008777386
Assignee:	Chengdu BOE Optoelectronics Technology Co., Ltd. (Sichuan, CN); BOE Technology Group Co., Ltd. (Beijing, CN)
Appl. No.:	17/789168
Filed (or PCT Filed):	August 10, 2021
PCT No.:	PCT/CN2021/111722
PCT Pub. No.:	WO2022/068409
PCT Pub. Date:	April 07, 2022

Prior Publication Data

Document Identifier

US 20230056754 A1

Publication Date

Feb. 23, 2023

Foreign Application Priority Data

CN

202011065609.9

Sep. 30, 2020

Publication Classification

Int. Cl.: H10K77/10 (20230101); H10K59/12 (20230101); H10K59/124 (20230101);
H10K59/35 (20230101); H10K71/00 (20230101); H10K102/00 (20230101)

U.S. Cl.:

CPC H10K77/111 (20230201); H10K59/124 (20230201); H10K71/00 (20230201);
H10K59/1201 (20230201); H10K59/352 (20230201); H10K2102/311 (20230201)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2008/0218369	12/2007	Krans	313/511	A47G 11/003
2016/0035806	12/2015	Park	257/40	H10K 59/121
2019/0081273	12/2018	Sung	N/A	H10K 50/844
2020/0057330	12/2019	Yamazaki	N/A	H10K 59/121
2020/0127233	12/2019	Sung	N/A	H10K 59/121
2020/0136068	12/2019	Lee	N/A	H10K 59/122
2020/0152842	12/2019	Park	N/A	H01L 27/15
2020/0235179	12/2019	Baik et al.	N/A	N/A
2020/0328269	12/2019	Shin	N/A	H10K 59/8731
2020/0365825	12/2019	Yu	N/A	N/A
2021/0273029	12/2020	Bang	N/A	H10K 59/122

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
110224006	12/2018	CN	N/A
110311057	12/2018	CN	N/A
111180485	12/2019	CN	N/A
111293235	12/2019	CN	N/A
111341210	12/2019	CN	N/A
111490071	12/2019	CN	N/A
111564482	12/2019	CN	N/A
111653595	12/2019	CN	N/A

OTHER PUBLICATIONS

International Search Report for PCT/CN2021/111722 Mailed Nov. 11, 2021. cited by applicant
Office Action dated Nov. 2, 2021 for Chinese Patent Application No. 202011065609.9 and English Translation. cited by applicant

Decision to Grant dated Apr. 8, 2022 for Chinese Patent Application No. 202011065609.9 and English Translation. cited by applicant

Primary Examiner: Maldonado; Julio J

Assistant Examiner: Das; Pinaki

Attorney, Agent or Firm: Ling and Yang Intellectual Property

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) The present application is a U.S. National Phase Entry of International Application PCT/CN2021/111722 having an international filing date of Aug. 10, 2021, which claims priority of Chinese Patent Application No. 202011065609.9, filed to the CNIPA on Sep. 30, 2020 and entitled “Display Substrate and Manufacturing Method Therefor, and Display Device”, the contents disclosed in the above-mentioned applications are hereby incorporated as a part of this application.

TECHNICAL FIELD

(2) Embodiments of the present disclosure relate to, but are not limited to, the field of display technologies, and in particular to a display substrate and a method for manufacturing the display substrate, and a display device.

BACKGROUND

(3) Organic Light Emitting Diode (OLED) display technology has been developed rapidly in recent years because of its large viewing angle, high brightness, fast response, low power consumption, and flexibility, and it is considered as the most potential display technology. With the development of society and the progress of technology, people have higher and higher requirements for screen proportions of electronic products, and full screen is the general trend. However, in order to realize a real full screen, the four corners of the screen need to be made into a locally stretchable structure to adapt to a subsequent module bonding process. A deep hole design of an OLED flexible substrate may achieve local stretching function, which is one of important directions for realizing full screen technology.

(4) In a design of an OLED flexible substrate with a deep hole, a common layer of an OLED device will easily to absorb water from the outside after evaporation to the deep hole, which leads to failure of luminescent materials, resulting in local display failure. In some technologies, a separation structure is provided around the deep hole to separate the common layer of the OLED device, so as to achieve a purpose of blocking water and oxygen intrusion channels, and ensure a packaging effect while achieving the local stretching function. However, in this scheme, a new separation structure manufacturing process and a corresponding mask need to be introduced, and the separation structure will occupy space, which reduces the pixel density and affect the display effect.

SUMMARY

(5) The following is a summary of subject matters described herein in detail. The summary is not

intended to limit the protection scope of claims.

(6) An embodiment of the present disclosure provides a display substrate, including a stretchable area; the stretchable area includes multiple pixel island areas spaced apart from each other, multiple hole areas, and connection bridge areas located between the pixel island areas and the hole areas; each of the hole areas is provided with one or more apertures and includes a composite structural layer stacked on a base substrate, the one or more apertures penetrate through the composite structural layer and a portion of an aperture is provided in the base substrate, the aperture penetrates through or does not penetrate through the base substrate, and a wall of the aperture is provided with separation grooves; each of the hole areas further includes a functional film layer provided on the composite structural layer and on the wall of the aperture, and the functional film layer is separated at the separation grooves.

(7) An embodiment of the present disclosure further provides a display device including the display substrate.

(8) An embodiment of the present disclosure further provides a method for manufacturing a display substrate; the display substrate includes a stretchable area; the stretchable area includes multiple pixel island areas spaced apart from each other, multiple hole areas, and connection bridge areas located between the pixel island areas and the hole areas; each of the hole area is provided with one or more apertures which penetrate through or do not penetrate through a base substrate; the manufacturing method includes: forming a composite structural layer on the base substrate of the hole areas, wherein the base substrate includes a flexible layer and a barrier layer that are stacked, the composite structural layer includes an inorganic composite insulating layer provided on the barrier layer and an organic composite layer provided on the inorganic composite insulating layer; forming a first opening on the organic composite layer, wherein the first opening exposes a surface of the inorganic composite insulating layer; forming a second opening on a portion of the inorganic composite insulating layer exposed by the first opening, wherein the second opening penetrates through the barrier layer and exposes a surface of the flexible layer; forming a third opening on the flexible layer, wherein the third opening penetrates through or does not penetrate through the flexible layer, an orthographic projection of the third opening on the base substrate includes an orthographic projection of the second opening on the base substrate, the first opening, the second opening, and the third opening form an aperture, the third opening forms a separation groove with respect to an enlarged portion of the second opening in a direction parallel to the base substrate, and the separation groove is provided on a wall of the aperture; and forming a functional film layer on the composite structural layer, wherein the functional film layer is provided on the wall of the aperture and is separated at the separation groove.

(9) Other aspects may be understood upon reading and understanding of the drawings and the detailed description.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) The accompanying drawings are used for providing understanding of technical solutions of the present disclosure, and form a part of the specification. They are used for explaining the technical solutions of the present disclosure together with the embodiments of the present disclosure, and do not form a limitation on the technical solutions of the present disclosure.

(2) FIG. 1 is a schematic diagram of a deep hole and a separation structure of some hole areas of a display substrate.

(3) FIG. 2a is a schematic diagram of a planar structure of a stretchable area of a display substrate according to an embodiment of the present disclosure.

(4) FIG. 2b is a schematic diagram of a planar structure of another stretchable area of a display

substrate according to an embodiment of the present disclosure.

(5) FIG. 2c is a schematic diagram of a cross-sectional structure at a position A-A in FIG. 2a.

(6) FIG. 3 is a schematic diagram of a structure after a base substrate of a display substrate is formed in some exemplary embodiments.

(7) FIG. 4 is a schematic diagram of a structure after a drive structure layer of a pixel island area and an inorganic composite insulating layer of a hole area are formed in a display substrate in some exemplary embodiments.

(8) FIG. 5 is a schematic diagram of a structure after a planarization layer, an anode and a pixel definition layer of a pixel island area, and an organic composite layer forming a hole area are formed, and a first via hole and a second via hole are formed on the organic composite layer in a display substrate in some exemplary embodiments.

(9) FIG. 6 is a schematic diagram of a structure after a third via hole of a third barrier layer are formed on an inorganic composite insulating layer of a hole area that penetrates through a base substrate in some exemplary embodiments.

(10) FIG. 7a is a schematic diagram of a structure after a fourth via hole and a first separation groove are formed on a third flexible layer of a base substrate of a hole area in some exemplary embodiments.

(11) FIG. 7b is a schematic diagram of a structure after a fourth via hole and a first separation groove are formed on a third flexible layer of a base substrate of a hole area in some other exemplary embodiments.

(12) FIG. 8a is a schematic diagram of a structure after a fifth via hole is formed on a second barrier layer of a base substrate of a hole area in some exemplary embodiments.

(13) FIG. 8b is a schematic diagram of a structure after a fifth via hole is formed on a second barrier layer of a base substrate of a hole area in some other exemplary embodiments.

(14) FIG. 9 is a schematic diagram of a structure after a sixth via hole and a second separation groove are formed on a second flexible layer of a base substrate of a hole area in some exemplary embodiments.

(15) FIG. 10a is a schematic diagram of a structure after a seventh via hole is formed on a first barrier layer and a groove and a third separation groove are formed on a first flexible layer of a base substrate of a hole area in some exemplary embodiments.

(16) FIG. 10b is a schematic diagram of a structure after a seventh via hole is formed on a first barrier layer and an eighth via hole and a third separation groove are formed on a first flexible layer of a base substrate of a hole area in other some exemplary embodiments.

(17) FIG. 11a is a schematic diagram of a structure after an organic functional layer and a cathode are formed in some exemplary embodiments.

(18) FIG. 11b is a schematic diagram of a partially enlarged structure at position A in FIG. 11a.

DETAILED DESCRIPTION

(19) Those of ordinary skills in the art should understand that modifications or equivalent replacements may be made to the technical solutions of the embodiments of the present disclosure without departing from the spirit and scope of the technical solutions of the embodiments of the present disclosure, and should fall within the scope of the claims of the present disclosure.

(20) In some techniques, as shown in FIG. 1, a stretchable area of an OLED display substrate is provided with a deep hole **01** that penetrates or does not penetrate through a flexible base substrate. An separation structure **02** is provided around the deep hole **01**, wherein the separation structure **02** is a groove structure, and a cross-sectional area of a notch of the groove is smaller than a cross-sectional area of the rest of the groove. A common layer of an evaporated OLED device (such as an organic light emitting layer and a cathode) is separated at the separation structure **02** to form a first portion on a side of the separation structure **02** close to the deep hole **01**, and a second portion located on a side of the separation structure **02** away from the deep hole **01**. The second portion includes the common layer of the OLED device in a pixel area, so that water and oxygen in the first

portion will not intrude into the second portion, thus achieving a purpose of blocking the water and oxygen intrusion channels. However, in this scheme, a new separation structure manufacturing process and a corresponding mask need to be introduced, and the separation structure will occupy space, reduce a pixel density and affect a display effect.

(21) An embodiment of the present disclosure provides a display substrate including a stretchable area. In some exemplary embodiments, as shown in FIG. 2a, a structure of a portion of the stretchable area may be seen as a repetitive unit of the stretchable area. The stretchable area includes multiple pixel island areas **100** spaced apart from each other, multiple hole areas **300**, and connection bridge areas **200** located between the pixel island areas **100** and the hole areas **300**. Each pixel island area **100** may be surrounded by multiple hole areas **300**, a connection bridge area **200** is located between adjacent hole areas **300** and is connected with an adjacent pixel island area **100**, and light emitting devices of the multiple pixel island areas **100** are in signal communication through connection lines of the connection bridge areas **200**. Each hole area **300** is provided with one or more aperture that penetrate or not penetrate through the base substrate of the display substrate. The base substrate of the display substrate may be a flexible base substrate so that the stretchable area of the display substrate can be stretched. The pixel island areas **100** are configured to display an image, the hole areas **300** are configured to provide deformation space upon stretching, and the connection bridge areas **200** are configured to route (to implement signal communication between adjacent pixel island areas **100**) and transmit a pulling force. Each pixel island area **100** may include multiple pixel units. Each pixel unit includes multiple sub-pixels emitting light of different colors, for example, each pixel unit includes three sub-pixels, i.e., a first sub-pixel **110**, a second sub-pixel **120**, and a third sub-pixel **130**, which may be configured to emit red light, green light, and blue light, respectively. By adjusting the luminance of multiple sub-pixels of each pixel unit, the corresponding pixel unit can basically display any desired color. Each sub-pixel of the pixel island area **100** includes one light emitting device, wherein each light emitting device may be an OLED device, including an anode, an organic light emitting layer, and a cathode that are stacked, the organic light emitting layer emitting light under a voltage between the anode and the cathode. When the stretchable area is stretched under the action of an external force, deformation mainly occurs in the connection bridge areas **200**, and the light emitting devices in the pixel island areas **100** remain basically in shape and are not damaged.

(22) In some exemplary embodiments, A shape of each pixel island area may be rectangular or circular or the like in a plane parallel to the display substrate. A shape of each hole area may be rectangular, arc, T-shaped, L-shaped, I-shaped, etc. In some examples, as shown in FIG. 2a, the hole areas **300** are rectangular in shape, and each hole area **300** may be regarded as an aperture (i.e., aperture **301** hereafter). The aperture is rectangular in shape. In a plane parallel to the display substrate, the rectangular aperture may have a width of 5 microns to 20 microns and a length of 50 microns to 800 microns, e.g. 400 microns. In some other exemplary embodiments, as shown in FIG. 2b, FIG. 2b shows another structure of a portion of the stretchable area, which may be seen as a repetitive unit of the stretchable area. In FIG. 2b, the hole areas **300** have an arc shape, and each hole area **300** may be regarded as an aperture. The aperture has an arc shape. In a plane parallel to the display substrate, a diameter of the arc-shaped aperture may be 50 microns to 500 microns, for example 200 microns.

(23) In some exemplary embodiments, as shown in FIG. 2c, FIG. 2c is a cross-sectional view at a position A-A in FIG. 2a, the display substrate according to the embodiment of the present disclosure includes a stretchable area. The stretchable area includes multiple pixel island areas **100** spaced apart from each other, multiple hole areas **300**, and connection bridge areas **200** located between the pixel island areas **100** and the hole areas **300**. Each of the hole areas **300** is provided with one or more aperture **301** and the hole area **300** includes a composite structural layer stacked on a base substrate **10**. The aperture **301** penetrates through the composite structural layer and a part of the aperture **301** is provided in the base substrate **10**, the aperture **301** penetrates through or

does not penetrate through the base substrate **10**, and a wall of the aperture **301** is provided with separation grooves (in some examples, the separation grooves include a first separation groove **302A**, a second separation groove **302B** and a third separation groove **302C**). The hole area **300** further includes a functional film layer provided on the composite structural layer and on the wall of the aperture **301**, wherein the functional film layer is separated at the separation grooves.

(24) According to the display substrate of the embodiment of the present disclosure, the separation grooves are provided on the wall of the aperture **301** of the hole area **300**. The functional film layer is separated at the separation grooves on the wall of the aperture **301**, that is, the functional film layer located on a side of the separation grooves close to a back surface of the base substrate **10** (i.e., a surface of the base substrate **10** facing away from the display side) (this portion of the functional film layer is referred to as a first portion) is no longer connected with the functional film layer located on a side of the separation grooves away from the back surface of the base substrate **10** (this portion of the functional film layer is referred to as a second portion). The second portion includes the functional film layer located in the pixel island area **100**. In this way, after the functional film layer is separated by the separation grooves, water and oxygen of the first portion will not intrude into the second portion, so that the separation grooves may block the path of external water and oxygen entering the display substrate along the functional film layer, thus ensuring the packaging effect. In addition, since the separation grooves are provided on the wall of the aperture **301**, the stretching function of the stretchable area can be ensured. Moreover, the separation grooves do not occupy an extra space outside the aperture **301** and therefore will not reduce the pixel density. During the formation of the separation grooves, a mask plate is not needed, which can effectively reduce production costs and improve production efficiency.

(25) In some exemplary embodiments, the stretchable area may be located close to an edge of the display substrate or may be located in a middle area of the display substrate. In one example of the embodiment, the display substrate is rectangular, and the stretchable areas may be provided at four corners or at positions close to four side edges of the rectangular display substrate, thereby implementing the stretchable function of corresponding local areas of the display substrate.

(26) In some exemplary embodiments, the base substrate includes a flexible layer and a barrier layer that are stacked, and the flexible layer is provided with the separation grooves. The base substrate may be provided with a flexible layer or multiple flexible layers. In one example of the embodiment, the base substrate includes multiple flexible layers and multiple barrier layers, wherein the flexible layers and the barrier layers are alternately provided, and at least one of the flexible layers is provided with the separation grooves. As shown in FIG. 2c, the base substrate **10** includes a first flexible layer **10A**, a first barrier layer **10B**, a second flexible layer **10C**, a second barrier layer **10D**, a third flexible layer **10E** and a third barrier layer **10F** that are stacked. The composite structural layer is provided on the third barrier layer **10F**, the third flexible layer **10E** is provided with a first separation groove **302A**, the second flexible layer **10C** is provided with a second separation groove **302B**, and the first flexible layer **10A** is provided with a third separation groove **302C**.

(27) In this example, the first flexible layer **10A**, the second flexible layer **10C** and the third flexible layer **10E** may be made of polyimide (PI), or polyethylene terephthalate (PET), or other materials. The first barrier layer **10B**, the second barrier layer **10D**, and the third barrier layer **10F** may be made of an inorganic material such as silicon nitride (SiNx) or silicon oxide (SiOx) or the like. The base substrate **10** may further include a first amorphous silicon (a-si) layer provided between the first barrier layer **10B** and the second flexible layer **10C**, and a second amorphous silicon layer provided between the second barrier layer **10D** and the third flexible layer **10E**. An amorphous silicon layer may increase a binding force between a barrier layer and a flexible layer, so that after the flexible layer is formed on the barrier layer, it is ensured that the flexible layer can be firmly attached to the barrier layer.

(28) In some exemplary embodiments, the separation grooves may be provided in a circumferential

direction of the aperture **301** in a closed annular structure and the separation grooves may have a same shape as the aperture **301**, as shown in FIG. **2c**. A cross-sectional shape of the separation grooves in a direction perpendicular to the base substrate **10** may be rectangular, trapezoidal, semi-elliptical or other irregular patterns. A first groove surface **3021** of a separation groove may be a curved surface (such as a cambered surface) or an inclined surface or the like. A depth of the separation groove in a direction parallel to the base substrate **10** may gradually increase in a direction away from the base substrate **10**. The depth of the separation groove in the direction parallel to the base substrate **10** and its width in the direction perpendicular to the base substrate **10** may be designed as desired, provided that the organic functional layer **22** can be ensured to be separated at the separation groove.

(29) In some exemplary embodiments, the aperture **301** is rectangular in shape, and the aperture **301** has a width of 5 microns to 20 microns and a length of 50 microns to 800 microns. In other examples, the aperture **301** has an arc shape and the aperture **301** has a diameter of 50 microns to 500 microns.

(30) In some exemplary embodiments, the depth of the separation groove in the direction parallel to the base substrate **10** is greater than or equal to 0.5 microns. Each of the flexible layers has a thickness of 5 microns to 12 microns.

(31) In some exemplary embodiments, as shown in FIG. **11b**, FIG. **11b** shows a schematic diagram of a structure in which a functional film layer of the hole area **300** is formed within the aperture **301**. An inner surface of a separation groove (the first separation groove **302A**, the second separation groove **302B** and the third separation groove **302C** are shown in this example) includes a first groove surface **3021** facing the aperture **301**, a second groove surface **3022** facing the back side of the base substrate **10** (i.e., a side of the base substrate **10** facing away from the display side), and a third groove surface **3023** opposite the second groove surface **3022**.

(32) In some exemplary embodiments, as shown in FIG. **11b**, the first groove surface **3021**, the second groove surface **3022**, and the third groove surface **3023** are each formed by a flexible layer where the separation groove is located. In FIG. **11b**, the first separation groove **302A** is formed in the third flexible layer **10E**, the second separation groove **302B** is formed in the second flexible layer **10C**, and the third separation groove **302C** is formed in the first flexible layer **10A**. The third flexible layer **10E** forms the first groove surface **3021**, the second groove surface **3022** and the third groove surface **3023** of the first separation groove **302A**. The second flexible layer **10C** forms the first groove surface **3021**, the second groove surface **3022** and the third groove surface **3023** of the second separation groove **302B**. The first flexible layer **10A** forms the first groove surface **3021**, the second groove surface **3022** and the third groove surface **3023** of the third separation groove **302C**.

(33) In some exemplary embodiments, the first groove surface is formed by the flexible layer where the separation groove is located.

(34) The second groove surface is jointly formed by the flexible layer where the separation groove is located and a film layer provided on a side surface of the flexible layer away from the back side of the base substrate, or the second groove surface is formed by a film layer provided on a side surface of the flexible layer where the separation groove is located away from the back side of the base substrate.

(35) The third groove surface is jointly formed by the flexible layer where the separation groove is located and a film layer provided on a side surface of the flexible layer facing the back side of the base substrate, or the third groove surface is formed by a film layer provided on a side surface of the flexible layer where the separation groove is located facing the back side of the base substrate.

(36) In some exemplary embodiments, as shown in FIG. **11b**, the functional film layer **303** is further provided on the first groove surface **3021**, the second groove surface **3022**, and the third groove surface **3023** of the separation groove, and the functional film layer **303** is separated at an intersection of the first groove surface **3021** and the second groove surface **3022** (positions

indicated by P1 and P2 in FIG. 11b). The functional film layer 303 becomes thinner in the vicinity of the intersection of the first groove surface 3021 and the second groove surface 3022. The functional film layer 303 may be formed by an evaporation process in the manufacturing process. (37) In some exemplary embodiments, the pixel island area 100 includes a drive structure layer provided on the base substrate 10 and multiple light emitting devices provided on the drive structure layer. The drive structure layer includes a pixel driving circuit, and each of the multiple light emitting devices includes an anode 20, an organic functional layer 22, and a cathode 23 that are stacked. The organic functional layer 22 includes an organic light emitting layer. The functional film layer includes a first functional film layer and a second functional film layer that are stacked, wherein the first functional film layer has a same material as one film layer of the organic functional layers 22 of any one of the light emitting devices, and the second functional film layer has a same material as the cathode 23.

(38) In an example of the present embodiment, the pixel driving circuit includes multiple thin film transistors and a storage capacitor, and the anode 20 of the light emitting device is connected to a drain electrode of one of the thin film transistors. The light emitting device may be an OLED device. The organic functional layer 22 includes an organic light emitting layer, and may further include a hole injection layer, a hole transport layer, and an electron blocking layer that are stacked between the organic light emitting layer and the anode 20, and a hole barrier layer, an electron transport layer, and an electron injection layer that are stacked between the organic light emitting layer and the cathode 23. The organic light emitting layer emits light under a voltage between the anode 20 and the cathode 23.

(39) In an example of the present embodiment, each pixel island area 100 may include multiple pixel units, wherein each pixel unit includes multiple sub-pixels emitting light of different colors. For example, each pixel unit includes a red sub-pixel, a green sub-pixel, and a blue sub-pixel. By adjusting the luminance of multiple sub-pixels of each pixel unit, a corresponding pixel unit can basically display any desired color. Each sub-pixel of the pixel island area 100 includes a light emitting device, and the pixel island area 100 includes multiple sub-pixels arranged in an array. In some examples, all sub-pixels of the pixel island area 100 have one or more common film layers, wherein each of the one or more common film layers is in an integral structure and may cover the pixel island area 100, the connection bridge area 200 and the hole area 300. The common film layer may be any one or more of the organic functional layers 22 in one of the light emitting devices, and the cathode 23 in the light emitting device, as shown in FIG. 2c. FIG. 2c shows a light emitting device of a sub-pixel whose organic functional layer 22 and cathode 23 are common film layers for all sub-pixels of the pixel island area 100. The common film layer is formed on the wall of the aperture 301 after being evaporated into the aperture 301 of the hole area 300 and is disconnected at a separation groove on the wall of the aperture 301. The common film layer may form two portions after being separated by the separation groove (e.g., in an example where one separation groove is provided). The first portion is located on a side of the separation groove close to the back surface of the base substrate 10 (i.e., the surface of the base substrate facing away from the display side). The second portion is located on a side of the separation groove away from the back surface of the base substrate 10, and includes a portion of the common film layer located in the pixel island area 100. The water and oxygen of the first portion does not intrude into the second portion, thereby, the common film layer located in the pixel island area 100 will not be eroded by the water and oxygen.

(40) In an example of the present embodiment, a film-layer structure of the functional film layer of the hole area 300 may be related to the type and number of the common film layer(s) in the organic functional layer of the multiple light emitting devices in the pixel island area 100. For example, in some examples, if all the film layers in the organic functional layer 22 of a light emitting device R are common film layers and the cathode 23 of the light emitting device R is also a common film layer, the functional film layer of the hole area 300 may include all the film layers of the organic

functional layer **22** and the cathode **23** of the light emitting device **R** that are stacked.

(41) In some exemplary embodiments, as shown in FIG. **2c**, the composite structural layer includes an inorganic composite insulating layer **305** provided on the base substrate **10**, and an organic composite layer **304** provided on the inorganic composite insulating layer **305**. A side surface of the inorganic composite insulating layer **305** facing the aperture **301** protrudes from a side surface of the organic composite layer **304** facing the aperture **301** in a direction parallel to the base substrate **10**.

(42) In some exemplary embodiments, as shown in FIG. **2c**, the organic composite layer **304** includes a first organic layer (e.g., a planarization layer **19**) provided on the inorganic composite insulating layer **305**, and a second organic layer (e.g., a pixel definition layer **21**) provided on the first organic layer. The side surface of the inorganic composite insulating layer **305** facing the aperture **301** is flush in a direction parallel to the base substrate **10**. A side surface of the first organic layer facing the aperture **301** protrudes from a side surface of the second organic layer facing the aperture **301**, and the side surface of the inorganic composite insulating layer **305** facing the aperture **301** protrudes from the side surface of the first organic layer facing the aperture **301**.

(43) A structure of a display substrate according to the present disclosure is described below by an example of a manufacturing process of a display substrate. A “patterning process” mentioned in the present disclosure includes treatments such as film layer deposition, photoresist coating, mask exposure, development, etching, photoresist stripping, etc. The deposition may be any one or more of sputtering, evaporation, and chemical vapor deposition. The coating may be any one or more of spray coating and spin coating. The etching may be any one or more of dry etching and wet etching. A “thin film” refers to a thin film layer prepared from a material on a substrate by a process of deposition or coating. If a patterning process is not needed by a “thin film” throughout a whole preparation process, the “thin film” may also be referred to as a “layer”. When a patterning process is also needed by a “thin film” throughout a whole preparation process, the thin film is referred to as a “thin film” before the patterning process and referred to as a “layer” after the patterning process. The “layer” after the patterning process includes at least one “pattern”. That “A and B are arranged in the same layer” mentioned in the present disclosure refers to that A and B are simultaneously formed by a same patterning process. “An orthographic projection of A contains an orthographic projection of B” refers to that the orthographic projection of B falls in a range of the orthographic projection of A or the orthographic projection of A covers the orthographic projection of B.

(44) In some exemplary embodiments, the manufacturing process of the display substrate shown in FIG. **2c** may include the following steps.

(45) (1) A flexible base substrate **10** is manufactured on a glass carrier plate **1**.

(46) In an example of the embodiment of the present disclosure, the flexible base substrate **10** may have a three-layer flexible layer structure. The flexible base substrate **10** includes a first flexible material layer, a first inorganic material layer, a second flexible material layer, a second inorganic material layer, a third flexible material layer and a third inorganic material layer which are sequentially stacked on a carrier plate **1** (may be but not limited to glass material). The first flexible material layer, the second flexible material layer and the third flexible material layer may be made of Polyimide (PI), Polyethylene Terephthalate (PET), or a polymer soft film subjected to a surface treatment, etc. The first inorganic material layer, the second inorganic material layer and the third inorganic material layer may be made of silicon nitride (SiNx) or silicon oxide (SiOx), etc, for improving water and oxygen resistance of the base substrate. The first inorganic material layer, and the second inorganic material layer and the third inorganic material layer are called barrier layers. The flexible base substrate **10** may further include a first semiconductor layer provided between the first inorganic material layer and the second flexible material layer, and a second semiconductor layer provided between the second inorganic material layer and the third flexible material layer. The first semiconductor layer and the second semiconductor layer may be made of amorphous

silicon (a-si). The semiconductor layer may increase a bonding force between an inorganic material layer and a flexible material.

(47) In an exemplary embodiment, taking a laminated structure of PI1/Barrier1/PI2/Barrier2/PI3/Barrier3 as an example, the manufacturing process of the flexible base substrate **10** may include: first coating a layer of polyimide on the carrier plate **1**, and then forming a first flexible (PI1) layer **10A** after the polyimide is cured to form a film; then, depositing a layer of barrier thin film on the first flexible layer **10A** to form a first barrier (Barrier1) layer **10B** covering the first flexible layer **10A**; then, further coating a layer of polyimide on the first barrier layer **10B** to form a second flexible (PI2) layer **10C** after the polyimide is cured to form a film; then, depositing a layer of barrier thin film on the second flexible layer **10C** to form a second barrier (Barrier2) layer **10D** covering the second flexible layer **10C**; then further coating a layer of polyimide on the second barrier layer **10D** to form a third flexible (PI3) layer **10E** after the polyimide is cured to form a film; and then depositing a layer of barrier thin film on the third flexible layer **10E** to form a third barrier (Barrier3) layer **10F** covering the third flexible layer **10E**, thus completing the manufacturing of the flexible base substrate **10**, as shown in FIG. 3. After this process, the pixel island area **100**, the connection bridge area **200** and the hole area **300** each include a flexible base substrate **10**.

(48) In other examples, a one-layer flexible layer structure, a two-layer flexible layer structure or more than three-layer flexible layer structure may be used for the flexible base substrate **10**. The more the number of flexible layers, the larger the depth of the aperture **301** finally formed, and the better the tensile properties of the stretchable area.

(49) (2) Patterns of a drive structure layer and a connection line are manufactured on the flexible base substrate **10**, wherein the drive structure layer is formed in the pixel island area **100** and the connection line is formed in the connection bridge area **200**. The drive structure layer includes multiple gate lines and multiple data lines. The multiple gate lines and the multiple data lines cross perpendicularly to define multiple sub-pixels arranged in a matrix, wherein each sub-pixel is provided with a thin film transistor, as shown in FIG. 4. The manufacturing process of this step may include:

(50) a first insulating thin film and an active layer thin film are sequentially deposited on the flexible base substrate **10**, the active layer thin film is patterned by a patterning process to form a first insulating layer **11** covering the entire flexible base substrate **10** and a pattern of an active layer on the first insulating layer **11**. The pattern of the active layer is formed in the pixel island area **100**, and at least includes an active layer **12**. After this patterning process, the connection bridge area **200** and the hole area **300** include the first insulating layer **11** provided on the flexible base substrate **10**.

(51) Then, a second insulating thin film and a first metal thin film are sequentially deposited, and the first metal thin film is patterned by a patterning process to form a second insulating layer **13** covering the pattern of the active layer and a pattern of a first gate metal layer provided on the second insulating layer **13**. The pattern of the first gate metal layer includes a gate electrode **14A**, a first capacitor electrode **14B** and a gate line (not shown) formed in the pixel island area **100**, and a gate connection line (not shown) formed in the connection bridge area **200**. After this patterning process, the hole area **300** includes the first insulating layer **11** and the second insulating layer **13** stacked on the flexible base substrate **10**.

(52) Then, a third insulating thin film and a second metal thin film are sequentially deposited, and the second metal thin film is patterned by a patterning process to form a third insulating layer **15** covering the first gate metal layer and a pattern of a second gate metal layer provided on the third insulating layer **15**. The pattern of the second gate metal layer includes a second capacitor electrode **16** formed in the pixel island area **100**, wherein a position of the second capacitor electrode **16** corresponds to that of the first capacitor electrode **14B**. After this patterning process, the connection bridge area **200** and the hole area **300** include the first insulating layer **11**, the second insulating

layer **13** and the third insulating layer **15** which are stacked on the flexible base substrate **10**.
(53) Then, a fourth insulating thin film is deposited and a fourth inorganic insulating thin film is patterned by a patterning process to form a pattern of a fourth insulating layer **17** covering the second gate metal layer. The fourth insulating layer **17** is provided with two via holes, and the fourth insulating layer **17**, the third insulating layer **15** and the second insulating layer **13** in the two via holes are etched away to expose a surface of the active layer **12**. After this patterning process, the connection bridge area **200** and the hole area **300** include the first insulating layer **11**, the second insulating layer **13**, the third insulating layer **15** and the fourth insulating layer **17** which are stacked on the base substrate **10**.

(54) Subsequently, a third metal thin film is deposited and the third metal thin film is patterned by a patterning process to form a pattern of a third metal layer on the fourth insulating layer **17**. The pattern of the third metal layer includes a source electrode **18A**, a drain electrode **18B** and a data line (not shown) located in the pixel island area **100**, and a data connection line **18C** located in the connection bridge area **200**. The source electrode **18A** is connected to a surface of the active layer **12** facing away from the base substrate **10** through one via hole that penetrates through the fourth insulating layer **17**, the third insulating layer **15**, and the second insulating layer **13**, and the drain electrode **18B** is connected to the surface of the active layer **12** facing away from the base substrate **10** through another via hole that penetrates through the fourth insulating layer **17**, the third insulating layer **15**, and the second insulating layer **13**. After this patterning process, the film layer structure of the hole area **300** remains unchanged.

(55) At this point, the drive structure layer of the pixel island area **100** and the connection line in the connection bridge area **200** are manufactured on the flexible base substrate **10**. In the drive structure layer of the pixel island area **100**, the active layer **12**, the gate electrode **14A**, the source electrode **18A**, and the drain electrode **18B** constitute a thin film transistor **101**, wherein the thin film transistor **101** may be a driving transistor in the pixel driving circuit, and the drain electrode **18B** of the driving transistor is connected to an anode in the light emitting device. The first capacitor electrode **14B** and the second capacitor electrode **16** constitute a storage capacitor **102**. The connection bridge area **200** and the hole area **300** include an inorganic composite insulating layer **305** provided on the flexible base substrate **10**, wherein the inorganic composite insulating layer **305** includes the first insulating layer **11**, the second insulating layer **13**, the third insulating layer **15**, and the fourth insulating layer **17** that are stacked. The connection bridge area **200** further includes a gate connection line provided on the second insulating layer **13**, and a data connection line **18C** provided on the inorganic composite insulating layer **305**. The gate connection line is connected to gate lines in adjacent pixel island areas **100**, and the data connection line **18C** is may be connected to data lines in the adjacent pixel island areas **100** for signal communication between the adjacent pixel island areas **100**.

(56) In an exemplary embodiment, the first insulating thin film, the second insulating thin film, the third insulating thin film and the fourth insulating thin film may be made of any one or more of silicon oxide (SiOx), silicon nitride (SiNx) and silicon oxynitride (SiON), and may be of a single layer, multiple layers or a composite layer. The first insulating layer **11** is referred to as a buffer layer, which is used for improving capabilities of water and oxygen resistance of the flexible base substrate **10**. The second insulating layer **13** and the third insulating layer **15** are referred to as gate insulating (GI) layers. The fourth insulating layer **17** is referred to as an interlayer dielectric (ILD) layer. The first metal thin film, the second metal thin film and the third metal thin film may be made of metal materials, such as any one or more of silver (Ag), copper (Cu), aluminum (Al), titanium (Ti) and molybdenum (Mo), or an alloy material of the above metals, such as aluminum neodymium alloy (AlNd) or molybdenum niobium alloy (MoNb), and may have a single-layer structure or a multi-layer composite structure, such as Ti/Al/Ti. The active layer thin film may be made of materials, such as amorphous indium gallium zinc oxide (a-IGZO), zinc oxynitride (ZnON), indium zinc tin oxide (IZTO), amorphous silicon (a-Si), polycrystalline silicon (p-Si),

hexathiophene, and polythiophene. Namely, the present disclosure is applicable to transistors manufactured based on oxide technology, silicon technology and organic substances technology.

(57) (3) A planarization layer **19**, an anode **20**, and a pixel definition layer **21** are formed on the flexible base substrate **10** on which the aforementioned patterns are formed, as shown in FIG. 5. In some exemplary embodiments, the manufacturing process of this step may include:

(58) A planarization thin film of an organic material is coated on the flexible base substrate **10** on which the aforementioned patterns are formed to form a planarization (PLN) layer **19** covering the entire flexible base substrate **10**, a via hole is formed on the planarization layer **19** of the pixel island area **100** by masking, exposing and developing processes, and the planarization layer **19** in the via hole is developed away to expose a surface of the drain electrode **18B** of the thin film transistor **101**. After this patterning process, the connection bridge area **200** and the hole area **300** each include a planarization layer **19** provided on the fourth insulating layer **17**.

(59) A transparent conductive thin film is deposited on the flexible base substrate **10** on which the aforementioned patterns are formed and the transparent conductive thin film is patterned by a patterning process to form a pattern of an anode **20**. The anode **20** is formed on the planarization layer **19** of the pixel island area **100** and is connected to the drain electrode **18B** of the thin film transistor **101** through the via hole on the planarization layer **19**. In an exemplary embodiment, the transparent conductive thin film may be made of indium tin oxide (ITO) or indium zinc oxide (IZO).

(60) A pixel definition thin film is coated on the flexible base substrate **10** on which the aforementioned patterns are formed to form a pattern of a pixel definition layer (PDL) by masking, exposing and developing processes. The pixel definition layer **21** of the pixel island area **100** is provided with a pixel opening, and the pixel definition layer **21** in the pixel opening is developed to expose a surface of the anode **20**. The pixel definition layer **21** of the hole area **300** is provided with a first via hole **310**, wherein the first via hole **310** exposes a surface of the planarization layer **19**.

(61) A second via hole **320** is formed in a portion of the planarization layer **19** exposed by the first via hole **310**, and the planarization layer **19** in the second via hole **320** is developed to expose a surface of the fourth insulating layer **17**. An orthographic projection of the first via hole **310** on the flexible base substrate **10** may include an orthographic projection of the second via hole **320** on the flexible base substrate **10**. In the direction parallel to the base substrate **10**, a side surface of the planarization layer **19** facing the second via hole **320** protrudes from a side surface of the pixel definition layer **21** facing the first via hole **310**. The first via hole **310** and the second via hole **320** are collectively referred to as first openings.

(62) (4) A third via hole **330** is formed on a portion of the fourth insulating layer **17** of the hole area **300** exposed by the second via hole **320**. The third via hole **330** penetrates through the fourth insulating layer **17**, the third insulating layer **15**, the second insulating layer **13**, the first insulating layer **11** and the third barrier layer **10F** of the flexible base substrate **10**. The fourth insulating layer **17**, the third insulating layer **15**, the second insulating layer **13**, the first insulating layer **11** and the third barrier layer **10F** of the flexible base substrate **10** in the third via hole **330** are etched away, and the third via hole **330** exposes a surface of the third flexible layer **10E**. The orthographic projection of the second via hole **320** on the flexible base substrate **10** may include an orthographic projection of the third via hole **330** on the flexible base substrate **10**, as shown in FIG. 6.

(63) In a direction parallel to the base substrate **10**, side surfaces of the fourth insulating layer **17**, the third insulating layer **15**, the second insulating layer **13**, the first insulating layer **11**, and the third barrier layer **10F** of the flexible substrate **10** facing the third via hole **330** (which may be regarded as a wall of the third via hole **330**) are flush with each other and protrude from the side surface of the planarization layer **19** facing the second via hole **320**. The third via hole **330** is referred to as a second opening.

(64) (5) A fourth via hole **340A** and a first separation groove **302A** are formed on the third flexible layer **10E** of the hole area **300**, as shown in FIG. 7a. A portion of the third flexible layer **10E**

exposed by the third via hole **330** is completely etched away to form a fourth via hole **340A**. An orthographic projection of the fourth via hole **340A** on the flexible base substrate **10** may overlap with the orthographic projection of the third via hole **330** on the flexible base substrate **10**, or the orthographic projection of the fourth via hole **340A** on the flexible base substrate **10** may include the orthographic projection of the third via hole **330** on the flexible base substrate **10**. A side surface of the third flexible layer **10E** facing the fourth via hole **340A** forms the first separation groove **302A**, and a notch of the first separation groove **302A** faces the fourth via hole **340A** and communicates with the fourth via hole **340A**. The third flexible layer **10E** inside the first separation groove **302A** is etched away, and an inner surface of the first separation groove **302A** is formed by the third flexible layer **10E**. The inner surface of the first separation groove **302A** includes a first groove surface **3021** facing the fourth via hole **340A**, a second groove surface **3022** facing the back side of the flexible base substrate **10**, and a third groove surface **3023** facing away from the back side of the flexible base substrate **10**. The third groove surface **3023** is opposite to the second groove surface **3022**. The wall of the third via hole **330** protrudes from the first groove surface **3021** in the direction parallel to the base substrate **10**. In this example, the first groove surface **3021**, the second groove surface **3022** and the third groove surface **3023** of the first separation groove **302A** are all formed by the third flexible layer **10E**. In this example, the fourth via hole **340A** and the first separation groove **302A** are collectively referred to as a third opening.

(65) In some exemplary embodiments, as shown in FIG. **7b**, a fourth via hole **340B** is formed on the third flexible layer **10E**, the orthographic projection of the fourth via hole **340B** on the flexible base substrate **10** includes the orthographic projection of the third via hole **330** on the flexible base substrate **10**, and the third flexible layer **10E** in the fourth via hole **340B** is completely etched away. The wall of the third via hole **330** protrudes from the wall of the fourth via hole **340B** in the direction parallel to the base substrate **10**. In this example, the fourth via hole **340B** is referred to as a third opening.

(66) In this step, a material of the third flexible layer **10E** is PI, and an etching method may be used for the process of forming the third opening on the third flexible layer **10E**. Mixed gas of carbon tetrafluoride and oxygen (CF_4/O_2) may be used as etching gas. By adjusting a ratio of CF_4/O_2 in combination with a blocking effect of the second barrier layer **10D** on the etching gas (the etching gas for etching the third flexible layer **10E** has no effect on the second barrier layer **10D**), transverse etching may be achieved to etch a structure of the third opening satisfying requirements, that is, the structures of the fourth via hole **340A** and the first separation groove **302A** or the structure of the fourth via hole **340B** may be obtained by etching.

(67) In some examples, the first, second and third openings described above may form the aperture **301**, wherein the aperture **301** penetrates or does not penetrate through the base substrate **10**. A single-layer flexible structure or a multi-layer flexible layer structure may be used for the base substrate **10**.

(68) (6) A fifth via hole **350** is formed on the second barrier layer **10D** of the hole area **300**, as shown in FIG. **8a**. An orthographic projection of the fifth via hole **350** on the flexible base substrate **10** may overlap with the orthographic projection of the third via hole **330** on the flexible base substrate **10**. The wall of the fifth via hole **350** and the wall of the third via hole **330** may be flush in the direction parallel to the base substrate **10**. A first separation groove **302A** is formed on the third flexible layer **10E**.

(69) In some other examples, a fifth via hole **350** is formed on the second barrier layer **10D** of the hole area **300**, as shown in FIG. **8b**. An orthographic projection of the fourth via hole **340B** formed on the third flexible layer **10E** on the flexible base substrate **10** includes an orthographic projection of the third via hole **330** and the fifth via hole **350** on the flexible base substrate **10**. The wall of the fifth via hole **350** and the wall of the third via hole **330** are flush in the direction parallel to the base substrate **10** and both protrude from the wall of the fourth via hole **340B**. A portion of the third barrier layer **10F** protruding from the wall of the fourth via hole **340B** is a first protrusion, and a

portion of the second barrier layer **10D** protruding from the wall of the fourth via hole **340B** is a second protrusion. A surface of the first protrusion facing the base substrate **10**, a surface of the second protrusion facing away from the base substrate **10**, and the wall of the fourth via hole **340B** form an inner surface of the first separation groove **302A**. That is, in this example, the first groove surface **3021** of the first separation groove **302A** is formed by the third flexible layer **10E**, the second groove surface **3022** is formed by the surface of the first protrusion facing the base substrate **10**, and the third groove surface **3023** is formed by the surface of the second protrusion facing away from the base substrate **10**.

(70) In other examples, the first groove surface **3021** of the first separation groove **302A** is formed by the third flexible layer **10E**, the second groove surface **3022** may be jointly formed by the third flexible layer **10E** and the third barrier layer **10F**, and the third groove surface **3023** may be jointly formed by the third flexible layer **10E** and the second barrier layer **10D**.

(71) (7) A sixth via hole **360** and a second separation groove **302B** are formed on the second flexible layer **10C**. A method of forming the sixth via hole **360** and the second separation groove **302B** in this step may be the same as the method of forming the fourth via hole **340A** (or the fourth via hole **340B**) and the first separation groove **302A** on the third flexible layer **10E**, and a structure of the second separation groove **302B** may be the same as that of the first separation groove **302A**, as shown in FIG. **9**. FIG. **9** shows a structure in which the second separation groove **302B** is formed on the second flexible layer **10C**.

(72) (8) A seventh via hole **370** is formed on the first barrier layer **10B**. A method of forming the seventh via hole **370** on the first barrier layer **10B** in this step may be the same as the method of forming the fifth via hole **350** on the second barrier layer **10D**, and a structure of the seventh via hole **370** may be the same as that of the fifth via hole **350**, as shown in FIG. **10a**.

(73) (9) A groove **380A** and a third separation groove **302C** are formed on the first flexible layer **10A**, as shown in FIG. **10a**, wherein an orthographic projection of the groove **380A** on the base substrate **10** includes, for example, an orthographic projection of the seventh via hole **370** on the base substrate **10**. An orthographic projection of a notch of the groove **380A** on the base substrate **10** may overlap with the orthographic projection of the seventh via hole **370** on the base substrate **10**, or the orthographic projection of the notch of the groove **380A** on the base substrate **10** may include the orthographic projection of the seventh via hole **370** on the base substrate **10**.

(74) In the direction parallel to the base substrate **10**, the groove **380A** forms a third separation groove **302C** with respect to an enlarged portion of the wall of the seventh via hole **370**. An inner surface of the third separation groove **302C** may be formed by the first flexible layer **10A**, or an inner surface of the third separation groove **302C** may be jointly formed by portions of the first flexible layer **10A** and the first barrier layer **10B** facing the inside of the third separation groove **302C**. In this example, since the groove **380A** does not penetrate through the first flexible layer **10A**, the aperture **301** finally formed in the hole area **300** does not penetrate through the base substrate **10**.

(75) In some other examples, an eighth via hole **380B** and a third separation groove **302C** are formed on the first flexible layer **10A**, as shown in FIG. **10b**, wherein the eighth via hole **380B** penetrates through the first flexible layer **10A**. In this example, a method of forming the eighth via hole **380B** and the third separation groove **302C** may be the same as the method of forming the fourth via hole **340A** (or the fourth via hole **340B**) and the first separation groove **302A** on the third flexible layer **10E**, and a structure of the third separation groove **302C** may be the same as that of the first separation groove **302A**.

(76) In some examples, at this point, an aperture **301** and a separation groove are formed in the hole area **300**. The first via hole **310**, the second via hole **320**, the third via hole **330**, the fourth via hole **340A** (or the fourth via hole **340B**), the fifth via hole **350**, the sixth via hole **360**, the seventh via hole **370** and the groove **380A** (or the eighth via hole **380B**) form the aperture **301**, wherein the aperture **301** penetrates or does not penetrate through the base substrate **10**. In the foregoing

examples, three separation grooves, i.e., the first separation groove **302A**, the second separation groove **302B**, and the third separation groove **302C**, are provided on the wall of the aperture **301** in a direction perpendicular to the base substrate **10**, and the structures of the three separation grooves may be the same. The three separation grooves are respectively provided in the third flexible layer **10E**, the second flexible layer **10C** and the first flexible layer **10A** of the flexible base substrate **10**, and each of the flexible layers is provided with one of the separation grooves. The number of separation grooves provided on the wall of the aperture **301** may be equal to or less than the number of flexible layers of the flexible base substrate **10**. In other examples, the number of flexible layers of the flexible base substrate **10** may be one, two or more than three. In the direction perpendicular to the base substrate **10**, cross-sectional shapes of the first separation groove **302A**, the second separation groove **302B**, and the third separation groove **302C** may be rectangular, trapezoidal, semi-elliptical, or irregular.

(77) (10) An organic functional layer **22** and a cathode **23** are sequentially formed on the flexible base substrate **10** on which the aforementioned patterns are formed, as shown in FIG. **11a**.

(78) In some exemplary embodiments, both the organic functional layer **22** and the cathode **23** may be formed in the pixel island area **100**, the connection bridge area **200** and the hole area **300** using an evaporation process. The organic functional layer **22** of the pixel island area **100** and the connection bridge area **200** covers the pixel definition layer **21**, and the organic functional layer **22** of the pixel island area **100** is connected to the anode **20** exposed by a pixel opening of the pixel definition layer **21**. The organic functional layer **22** of the hole area **300** covers the wall of the aperture **301** and the separation grooves (including, for example, the first separation groove **302A**, the second separation groove **302B**, and the third separation groove **302C**). The cathode **23** is formed on the organic functional layer **22**, and the anode **20**, the organic functional layer **22** and the cathode **23** of the pixel island area **100** form a light emitting device. The cathode **23** may be made of any one or more of magnesium (Mg), silver (Ag), aluminum (Al), copper (Cu) and lithium (Li), or an alloy made of any one or more of the above metals.

(79) Due to the presence of the separation groove, the organic functional layer **22** formed by evaporation is separated at the separation groove, and an inner surface of the separation groove includes a first groove surface **3021** facing the aperture **301**, a second groove surface **3022** facing a back side of the base substrate **10**, and a third groove surface **3023** opposite to the second groove surface **3022**. Generally, the organic functional layer **22** is disconnected at an intersection of the first groove surface **3021** and the second groove surface **3022**, and a thickness of the organic functional layer **22** becomes thinner in the vicinity of the intersection of the first groove surface **3021** and the second groove surface **3022**, as shown in FIG. **11b**. FIG. **11b** is a partially enlarged view at position A in FIG. **11a**. Taking the first separation groove **302A** as an example, the organic functional layer **22** is disconnected at positions P1 and P2 in the sectional view. The organic functional layer **22** is also disconnected at respective positions in the second separation groove **302B** and the third separation groove **302C**. A depth of the separation groove in the direction parallel to the base substrate **10** and its width in the direction perpendicular to the base substrate **10** may be designed as required, as long as the organic functional layer **22** can be ensured to be disconnected at the separation groove. Similarly, the cathode **23** is formed on the organic functional layer **22**, and a position where the cathode **23** is disconnected at the separation groove corresponds to the position where the organic functional layer **22** is disconnected at the separation groove. Since both the organic functional layer **22** and the cathode **23** are disconnected at the separation groove, an intrusion path of water and oxygen is blocked, that is, the water and oxygen do not intrude into the organic functional layer **22** and the cathode **23** of the pixel island area **100**, thereby ensuring the packaging effect. The organic functional layer **22** and the cathode **23** may be separated at multiple separation grooves, that is, the organic functional layer **22** and the cathode **23** may be separated at of the multiple positions, thereby adding the multiple guarantee for separation. In addition, since each separation groove is provided on the wall of the aperture **301**, the separation groove does not

occupy extra space outside the aperture **301**, does not reduce the pixel density, and does not need a mask plate during the formation of the separation groove, thus saving costs.

(80) (11) An encapsulation structure layer **7** is formed on the flexible base substrate **10** on which the aforementioned patterns are formed. The encapsulation structure layer may include a first inorganic layer **24**, an organic encapsulation layer **25**, and a second inorganic layer **26** which are stacked. The first inorganic encapsulation layer **24** covers the cathode **23**, the organic encapsulation layer **25** is provided in the pixel island area **100**, and the second inorganic encapsulation layer **26** covers the first inorganic encapsulation layer **24** and the organic encapsulation layer **25**. The hole area **300** includes the first inorganic encapsulation layer **24** and the second inorganic encapsulation layer **26** that are stacked, wherein the first inorganic encapsulation layer **24** and the second inorganic encapsulation layer **26** cover the cathode **23** of the hole area **300** and encapsulate the organic functional layer **22** and the cathode **23**, as shown in FIG. 2c. The first inorganic encapsulation layer **24**, the organic encapsulation layer **25** and the second inorganic encapsulation layer **26** may be made by Chemical Vapor Deposition (CVD), sputtering, or other coating manners. The encapsulation structure layer serves to isolate water and oxygen, and can effectively prevent the contact between air and the organic functional layer **22** and the cathode **23**. Finally, the flexible base substrate **10** on which all the film layers have been manufactured is peeled off from the carrier plate **1** to obtain a display substrate.

(81) Based on the aforementioned contents, an embodiment of the present disclosure further provides a method for manufacturing a display substrate; the display substrate includes a stretchable area; the stretchable area includes multiple pixel island areas spaced apart from each other, multiple hole areas, and connection bridge areas located between the pixel island areas and the hole areas; each of the hole areas is provided with one or more apertures which penetrate through or do not penetrate through a base substrate; the manufacturing method includes: forming a composite structural layer on the base substrate of the hole areas, wherein the base substrate includes a flexible layer and a barrier layer that are stacked, the composite structural layer includes an inorganic composite insulating layer provided on the barrier layer and an organic composite layer provided on the inorganic composite insulating layer; forming a first opening on the organic composite layer, wherein the first opening exposes a surface of the inorganic composite insulating layer; forming a second opening on a portion of the inorganic composite insulating layer exposed by the first opening, wherein the second opening penetrates through the barrier layer and exposes a surface of the flexible layer; forming a third opening on the flexible layer, wherein the third opening penetrates through or does not penetrate through the flexible layer, an orthographic projection of the third opening on the base substrate includes an orthographic projection of the second opening on the base substrate, the first opening, the second opening, and the third opening form the aperture, the third opening forms a separation groove with respect to an enlarged portion of the second opening in a direction parallel to the base substrate, and the separation groove is provided on a wall of the aperture; and forming a functional film layer on the composite structural layer, wherein the functional film layer is provided on the wall of the aperture and is separated at the separation groove.

(82) An embodiment of the present disclosure further provides a display device, including the display substrate described in any one of the aforementioned embodiments. The display device may be any product or component with a display function, such as a mobile phone, a tablet computer, a television, a display, a laptop computer, a digital photo frame, or a navigator.

(83) In the description herein, orientation or positional relations indicated by terms “up”, “down”, “left”, “right”, “top”, “inside”, “outside”, “axial direction”, “four corners” and the like are based on the orientation or positional relations shown in the drawings, and are for ease and brief description of the present disclosure and are not intended to indicate or imply that the structures referred to must have a specific orientation, or be constructed and operated in a particular orientation, and therefore these terms should not be construed as limitations on the present disclosure.

(84) In the description herein, the terms “connection”, “fixed connection”, “installation” and “assembly” are to be understood in a broad sense, for example, a connection may be a fixed connection, or a detachable connection, or may be an integral connection, unless explicitly specified and defined otherwise. The terms “installation”, “connection” and “fixed connection” may refer to a direct connection, or may an indirect connection through an intermediate medium, or may be an internal connection between two elements. Those of ordinary skills in the art may understand the meanings of the above terms in the present disclosure.

Claims

1. A display substrate, comprising a stretchable area, wherein the stretchable area comprises a plurality of pixel island areas spaced apart from each other, a plurality of hole areas, and connection bridge areas located between the pixel island areas and the hole areas; each of the hole areas is provided with one or more apertures and comprises a composite structural layer stacked on a base substrate, the one or more apertures penetrate through the composite structural layer and a portion of an aperture is provided in the base substrate, the aperture penetrates through or does not penetrate through the base substrate, a wall of the aperture is provided with at least one separation groove, and an inner surface of the separation groove comprises a first groove surface facing the aperture, a second groove surface facing a back side of the base substrate, and a third groove surface opposite to the second groove surface; and each of the hole areas further comprises a functional film layer provided on the composite structural layer and on the first groove surface, the second groove surface and the third groove surface of the separation groove, the functional film layer becomes thinner in a vicinity of an intersection of the first groove surface and the second groove surface, and the functional film layer is disconnected at an intersection of the first groove surface and the second groove surface.
2. The display substrate according to claim 1, wherein the base substrate comprises a flexible layer and a barrier layer that are stacked, and the separation groove is provided on the flexible layer.
3. The display substrate according to claim 2, wherein the base substrate comprises a plurality of flexible layers and a plurality of barrier layers, the flexible layers and the barrier layers are alternately provided, and at least one of the flexible layers is provided with the separation groove.
4. The display substrate according to claim 3, wherein the base substrate comprises a first flexible layer, a first barrier layer, a second flexible layer, a second barrier layer, a third flexible layer and a third barrier layer that are stacked, the composite structural layer is provided on the third barrier layer, the third flexible layer is provided with a first separation groove, the second flexible layer is provided with a second separation groove, and the first flexible layer is provided with a third separation groove.
5. The display substrate according to claim 2, wherein the first groove surface, the second groove surface and the third groove surface are all formed by the flexible layer where the separation groove is located.
6. The display substrate according to claim 2, wherein the first groove surface is formed by the flexible layer where the separation groove is located; the second groove surface is jointly formed by the flexible layer where the separation groove is located and a film layer provided on a side surface of the flexible layer away from the back side of the base substrate, or the second groove surface is formed by a film layer provided on a side surface of the flexible layer where the separation groove is located away from the back side of the base substrate; and the third groove surface is jointly formed by the flexible layer where the separation groove is located and a film layer provided on a side surface of the flexible layer facing the back side of the base substrate, or the third groove surface is formed by a film layer provided on a side surface of the flexible layer where the separation groove is located facing the back side of the base substrate.
7. The display substrate according to claim 1, wherein the separation groove is provided in a

circumferential direction of the aperture, and has a closed annular structure.

8. The display substrate according to claim 1, wherein a pixel island area comprises a drive structure layer provided on the base substrate and a plurality of light emitting devices provided on the drive structure layer, the drive structure layer comprises a pixel driving circuit, each of the plurality of light emitting devices comprises an anode, an organic functional layer, and a cathode that are stacked, the organic functional layer comprises an organic light emitting layer, the functional film layer comprises a first functional film layer and a second functional film layer that are stacked, the first functional film layer has a same material as one film layer in the organic functional layer of any one of the light emitting devices, and the second functional film layer has a same material as the cathode.

9. The display substrate according to claim 1, wherein the composite structural layer comprises an inorganic composite insulating layer provided on the base substrate and an organic composite layer provided on the inorganic composite insulating layer, a side surface of the inorganic composite insulating layer facing the aperture protrudes from a side surface of the organic composite layer facing the aperture in a direction parallel to the base substrate.

10. The display substrate according to claim 9, wherein the organic composite layer comprises a first organic layer provided on the inorganic composite insulating layer, and a second organic layer provided on the first organic layer, a plurality of layers that constitute the inorganic composite insulating layer comprise side surfaces facing the aperture, with the side surfaces facing the aperture being flush provided, and in the direction parallel to the base substrate, a side surface of the first organic layer facing the aperture protrudes from a side surface of the second organic layer facing the aperture, and the side surfaces of the plurality of layers facing the aperture protrude from the side surface of the first organic layer facing the aperture.

11. The display substrate according to claim 1, wherein the aperture has a rectangular shape, and has a width of 5 microns to 20 microns and a length of 50 microns to 800 microns; or the aperture has an arc shape, and has a diameter of 50 microns to 500 microns.

12. The display substrate according to claim 1, wherein a depth of the separation groove in a direction parallel to the base substrate is greater than or equal to 0.5 microns.

13. The display substrate according to claim 2, wherein the flexible layer has a thickness of 5 microns to 12 microns.

14. A display device, comprising the display substrate according to claim 1.

15. A method for manufacturing a display substrate, the display substrate comprising a stretchable area, the stretchable area comprising a plurality of pixel island areas spaced apart from each other, a plurality of hole areas, and connection bridge areas located between the pixel island areas and the hole areas, each of the hole area being provided with one or more apertures which penetrate through or do not penetrate through a base substrate, wherein the method comprises: forming a composite structural layer on the base substrate of the hole areas, wherein the base substrate comprises a flexible layer and a barrier layer that are stacked, the composite structural layer comprises an inorganic composite insulating layer provided on the barrier layer and an organic composite layer provided on the inorganic composite insulating layer; forming a first opening in the organic composite layer, wherein the first opening exposes a surface of the inorganic composite insulating layer; forming a second opening in a portion of the inorganic composite insulating layer exposed by the first opening, wherein the second opening penetrates through the barrier layer and exposes a surface of the flexible layer; forming a third opening in the flexible layer, wherein the third opening penetrates through or does not penetrate through the flexible layer, an orthographic projection of the third opening on the base substrate comprises an orthographic projection of the second opening on the base substrate, the first opening, the second opening, and the third opening form an aperture, the third opening forms a separation groove with respect to an enlarged portion of the second opening in a direction parallel to the base substrate, and the separation groove is provided on a wall of the aperture, and an inner surface of the separation groove comprises a first

groove surface facing the aperture, a second groove surface facing a back side of the base substrate, and a third groove surface opposite to the second groove surface; and forming a functional film layer on the composite structural layer, wherein the functional film layer is provided on the first groove surface, the second groove surface and the third groove surface of the separation groove, the functional film layer becomes thinner in a vicinity of an intersection of the first groove surface and the second groove surface, and the functional film layer is disconnected at an intersection of the first groove surface and the second groove surface.

16. The method for manufacturing the display substrate according to claim 15, wherein the base substrate comprises a plurality of flexible layers and a plurality of barrier layers, the flexible layers and the barrier layers are alternately provided, and at least one of the flexible layers is provided with the separation groove.
