

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285953

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Chiang; Kai-Ming et al.

PACKAGE STRUCTURE AND MANUFACTURING METHOD THEREOF

Abstract

A package structure includes a first redistribution circuit structure, a semiconductor die, a connecting film, and a second redistribution circuit structure. The first redistribution circuit structure includes a dielectric structure and a routing structure disposed therein, where the dielectric structure includes a trench exposing the routing structure. The semiconductor die is disposed on and electrically coupled to the first redistribution circuit structure. The connecting film is disposed in the trench and between the semiconductor die and the first redistribution circuit structure, and the semiconductor die is thermally coupled to the routing structure through the connecting film. The second redistribution circuit structure is disposed on and electrically coupled to the semiconductor die, the second redistribution circuit structure is electrically coupled to the first redistribution circuit structure, and the semiconductor die is disposed between the first redistribution circuit structure and the second redistribution circuit structure.

Inventors: Chiang; Kai-Ming (Taichung City, TW), Tsai; Wei-Jhan (Kaohsiung City, TW), Weng; Sheng-Feng (Taichung City, TW), Lin; Ching-Yao (New Taipei City, TW), Yen; Ming-Yu (MiaoLi County, TW), Chang; Kai-Fung (Taipei City, TW), Lin; Chih-Wei (Hsinchu County, TW), Hsieh; Ching-Hua (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 88193627

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 19/216579

Filed: May 22, 2025

Related U.S. Application Data

parent US division 17709470 20220331 parent-grant-document US 12334424 child US 19216579

Publication Classification

Int. Cl.: **H01L23/498** (20060101); **H01L21/48** (20060101); **H01L23/00** (20060101);
H01L23/538 (20060101); **H01L25/065** (20230101); **H01L25/10** (20060101)

U.S. Cl.:

CPC **H01L23/49822** (20130101); **H01L21/4857** (20130101); **H01L21/486** (20130101);
H01L23/49816 (20130101); **H01L23/49838** (20130101); **H01L23/5383** (20130101);
H01L23/5386 (20130101); **H01L23/5389** (20130101); **H01L24/24** (20130101);
H01L24/32 (20130101); **H01L24/73** (20130101); **H01L25/105** (20130101); **H01L24/48**
(20130101); **H01L25/0657** (20130101); **H01L2224/24226** (20130101); **H01L2224/32145**
(20130101); **H01L2224/32225** (20130101); **H01L2224/32235** (20130101);
H01L2224/48228 (20130101); **H01L2224/73265** (20130101); **H01L2224/73267**
(20130101); **H01L2225/0651** (20130101); **H01L2225/06524** (20130101);
H01L2225/06568 (20130101); **H01L2225/1023** (20130101); **H01L2225/1041**
(20130101); **H01L2225/1058** (20130101); **H01L2225/1094** (20130101); **H01L2924/182**
(20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION [0001] This application is a divisional application of and claims the priority benefit of U.S. patent application Ser. No. 17/709,470, filed on Mar. 31, 2022, and now allowed. The entirety of the above-mentioned patent application is hereby incorporated by reference herein and made a part of this specification.

BACKGROUND

[0002] Semiconductor devices and integrated circuits are typically manufactured on a single semiconductor wafer. The dies of the wafer may be processed and packaged with other semiconductor devices or dies at the wafer level, and various technologies have been developed for the wafer level packaging.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0003] Aspects of the disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0004] FIG. 1 through FIG. 13 are schematic cross-sectional views of various stages in a manufacturing method of a package structure in accordance with some embodiments of the disclosure.

[0005] FIG. 14 is a schematic cross-sectional view of a package structure in accordance with some embodiments of the disclosure.

[0006] FIG. 15 is a schematic cross-sectional view of a package structure in accordance with some embodiments of the disclosure.

[0007] FIG. 16 is a flow chart illustrating a method of manufacturing a package structure in accordance with some embodiments of the disclosure.

[0008] FIG. **17** is a flow chart illustrating a method of manufacturing a redistribution circuit structure in accordance with some embodiments of the disclosure.

[0009] FIG. **18** is a flow chart illustrating a method of manufacturing a redistribution circuit structure in accordance with some alternative embodiments of the disclosure.

[0010] FIG. **19** through FIG. **22** are schematic cross-sectional views of various stages in a manufacturing method of a package structure in accordance with some alternative embodiments of the disclosure.

[0011] FIG. **23** is a schematic cross-sectional view of a package structure in accordance with some embodiments of the disclosure.

[0012] FIG. **24** is a schematic cross-sectional view of a package structure in accordance with some embodiments of the disclosure.

DETAILED DESCRIPTION

[0013] The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components, values, operations, materials, arrangements, or the like, are described below to simplify the disclosure. These are, of course, merely examples and are not intended to be limiting. Other components, values, operations, materials, arrangements, or the like, are contemplated. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0014] Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0015] In addition, terms, such as “first,” “second,” “third” and the like, may be used herein for ease of description to describe similar or different element(s) or feature(s) as illustrated in the figures, and may be used interchangeably depending on the order of the presence or the contexts of the description.

[0016] Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

[0017] Embodiments include a (semiconductor) package structure including a semiconductor die with a back-side redistribution circuit structure. In one scenario, due to the presence of the back-side redistribution circuit structure included in the package structure, an uneven outermost surface (e.g., an uneven topography, for example, a surface roughness of a surface peak to a surface valley being greater than or substantially equal to 4 μm (such as about 4 μm to about 7 μm)) of the back-side redistribution circuit structure, which is disposed with the semiconductor die, would cause air or void being trapped between the semiconductor die and the back-side redistribution circuit

structure after the semiconductor die being placing onto the back-side redistribution circuit structure. With the air or void trapped between the semiconductor die and the back-side redistribution circuit structure, an undesired movement of the semiconductor die and/or an insulating encapsulation surrounding the semiconductor die may occur during a thermal process, which reduces the reliability and performance of the package structure. In addition, with the air or void trapped between the semiconductor die and the back-side redistribution circuit structure, moisture may be trapped by the void and have the risk of “pop-corn” (e.g., water transfers from a liquid phase to a gas phase) during high temperature reliability test. Embodiments address this issue by utilizing an addition planarizing process on the back-side redistribution circuit structure prior to the placement of the semiconductor die, which is capable of providing a smooth outer surface of the back-side redistribution circuit structure, thereby facilitating the placement of the semiconductor die and enhancing the reliability and performance of the package structure.

[0018] In other scenarios, due to the presence of the back-side redistribution circuit structure in the package structure, a thermal dissipating distance for heat generated by the semiconductor die to the external is increased, which decreases the heat dissipation of the package structure. As a result, reliability and performance of the package structure may be reduced. Embodiments address this issue by utilizing a thermal conduction layer or film being disposed between the semiconductor die and the back-side redistribution circuit structure, adhering the semiconductor die directly onto conductive features included in the back-side redistribution circuit structure, or a combination thereof to facilitate the heat dissipation, thereby improving the reliability and performance of the package structure.

[0019] FIG. 1 through FIG. 13 are schematic cross-sectional views of various stages in a manufacturing method of a package structure **100a** in accordance with some embodiments of the disclosure. The embodiments are intended to provide further explanations but are not used to limit the scope of the disclosure. The formation of the package structure **100a** may be used in any of the embodiments relating to an enhancing element discussed below. FIG. 1 through FIG. 13 illustrate schematic cross-sectional views of intermediate steps of a process for forming the package structure **100a** until the package structure **100a** is ready to receive an additional component such as additional conductive terminals (for example, **184** as shown in FIG. 14) or/and an additional device such as another package (for example, **800** as shown in FIG. 15). In the disclosure, it should be appreciated that the illustration of components throughout all figures is schematic and is not in scale. FIG. 16 is a flow chart illustrating a method of manufacturing a package structure in accordance with some embodiments of the disclosure. FIG. 17 illustrates a flow chart illustrating a method of manufacturing a redistribution circuit structure of the package structure **100a** in accordance with some embodiments of the disclosure. In embodiments, the manufacturing method is part of a wafer level packaging process. It is to be noted that the process steps described herein cover a portion of the manufacturing processes used to fabricate a package structure.

[0020] Referring to FIG. 1, in some embodiments, a carrier substrate **102** is provided for the package structure **100a**, and a release layer **104** is formed on the carrier substrate **102**. The carrier substrate **102** may be a glass carrier substrate, a ceramic carrier substrate, or the like. The carrier substrate **102** may be a wafer, such that multiple packages can be formed on the carrier substrate **102** simultaneously. The release layer **104** may be formed of a polymer-based material (such as benzocyclobutene (BCB), polybenzoxazole (PBO)), which may be removed along with the carrier substrate **102** from the overlying structures that will be formed in subsequent steps.

[0021] In some embodiments, the release layer **104** is an epoxy-based thermal-release material, which loses its adhesive property when heated, such as a light-to-heat-conversion (LTHC) release coating. In other embodiments, the release layer **104** is an ultra-violet (UV) glue, which loses its adhesive property when exposed to UV lights. The release layer **104** may be dispensed as a liquid and cured, may be a lamination film laminated onto the carrier substrate **102**, or may be the like. An illustrated top surface of the release layer **104**, which is opposite to a bottom surface contacting

the carrier substrate **102**, may be leveled. For example, the illustrated top surface of the release layer **104** has high coplanarity to facilitate forming processes of the overlying structures. For example, the release layer **104** is a LTHC layer with good chemical resistance, and such layer enables room temperature debonding from the carrier substrate **102** by applying laser irradiation, however the disclosure is not limited thereto.

[0022] In some embodiments, a redistribution circuit structure **110** is formed on the release layer **104** and over the carrier substrate **102**, in accordance with step **S10** of FIG. **16** in conjunction with steps **S11a**, **S12a** and **S13a** of FIG. **17**. In some embodiments, as shown in FIG. **1** to FIG. **5**, the redistribution circuit structure **110** includes at least one dielectric layer **112** (e.g., **112a** and **112b**), at least one seed layer **114** (e.g., **114a** and **114b**), at least one conductive layer **116** (e.g., **116a** and **116b**), and a dielectric layer **118a**. However, in the disclosure, the numbers of layers of the dielectric layer **112**, the seed layer **114**, and the conductive layer **116** are not limited to what is depicted in FIG. **1** to FIG. **5**, where the numbers of the layers of the dielectric layer **112**, the seed layer **114**, and the conductive layer **116** may be one or more than one depending upon the demand and design requirements. In some embodiments, one conductive layer **116** includes a line portion extending along a horizontal direction (e.g., a direction X or Y), a via portion extending along a vertical direction (e.g., a direction Z) connecting to the line portion, or a combination thereof. The directions X, Y and Z may be different from each other. For example, as shown in FIG. **1**, the directions X, Y and Z are perpendicular to each other.

[0023] As illustrated in FIG. **1**, in some embodiments, a dielectric layer **112a** is formed on the release layer **104** and over the carrier substrate **102**. The dielectric layer **112a** is disposed on (e.g., in physical contact with) the release layer **104** and extends over (e.g., spans across) the illustrated top surface of the release layer **104**, as shown in FIG. **1**. In some embodiments, the dielectric layer **112a** is formed by, but not limited to, forming a blanket layer of dielectric material over the illustrated top surface of the release layer **104** to completely cover the release layer **104**. The material of the dielectric layer **112a** may be polyimide (PI), PBO, BCB, a nitride such as silicon nitride, an oxide such as silicon oxide, phosphosilicate glass (PSG), borosilicate glass (BSG), boron-doped phosphosilicate glass (BPSG), a combination thereof, or the like, which may be patterned using a photolithography and/or etching process. The etching process may include a dry etching, a wet etching, or a combination thereof. In some embodiments, the dielectric material blanket layer is formed by suitable fabrication techniques such as spin-on coating, chemical vapor deposition (CVD), (e.g., plasma-enhanced chemical vapor deposition (PECVD)), or the like.

[0024] Thereafter, a seed material layer **114m** is formed on the dielectric layer **112a** and over the release layer **104** and the carrier substrate **102**, for example. In some embodiments, the seed material layer **114m** is disposed on (e.g., in physical contact with) the dielectric layer **112a** and extends over an illustrated top surface of the dielectric layer **112a**. The seed material layer **114m** may be formed on the dielectric layer **112a** in a manner of a blanket layer made of metal or metal alloy materials; the disclosure is not limited thereto. In some embodiments, the seed material layer **114m** is referred to as a metal layer, which can be a single layer or a composite layer including a plurality of sub-layers formed of different materials. In some embodiments, the seed material layer **114m** includes titanium, copper, molybdenum, tungsten, titanium nitride, titanium tungsten, combinations thereof, or the like. For example, the seed material layer **114m** includes a titanium layer and a copper layer over the titanium layer.

[0025] The seed material layer **114m** may be formed through sputtering, physical vapor deposition (PVD), or the like. In some embodiments, the seed material layer **114m** is conformally formed on the dielectric layer **112a** by sputtering, and is in (physical) contact with the dielectric layer **112a** (e.g., its illustrated top surface). Throughout the description, the term “copper” is intended to include substantially pure elemental copper, copper containing unavoidable impurities, and copper alloys containing minor amounts of elements such as tantalum, indium, tin, zinc, manganese, chromium, titanium, germanium, strontium, platinum, magnesium, aluminum, or zirconium, etc. As

shown in FIG. 1, the conductive layer **116a** may include a plurality of line portions extending along the horizontal direction (e.g., the direction X and/or the direction Y). However, the disclosure is not limited thereto.

[0026] In some embodiments, after the formation of the seed material layer **114m**, a conductive layer **116a** is formed on the seed material layer **114m** and over the dielectric layer **112a**, as shown in FIG. 1. For example, the conductive layer **116a** is disposed on (e.g., in physical contact with) an illustrated top surface of the seed material layer **114m**. In some embodiments, the conductive layer **116a** is formed by, but not limited to, forming a first photo resist layer (not shown) over the seed material layer **114m**; patterning the first photo resist layer to form a plurality of first openings (not shown) penetrating the first photo resist layer and exposing portions of the seed material layer **114m** underneath thereto; and forming a first conductive material (not shown) in the first openings to be in (physical) contact with the exposed portions of the seed material layer **114m** to form the conductive layer **116a**. After the formation of the conductive layer **116a** in the first openings formed in the first photo resist layer, the first photo resist layer is removed. As shown in FIG. 1, the conductive layer **116a** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the seed material layer **114m**, where portions of the seed material layer **114m** may not be covered by the conductive layer **116a**.

[0027] The first photo resist layer may be formed by spin coating or the like, and may be exposed to light for patterning. In some embodiments, a material of the first photo resist layer includes a positive resist material or a negative resist material, that is suitable for a patterning process such as a photolithography process with a mask or a mask-less photolithography process (such as an electron-beam (e-beam) writing or an ion-beam writing). In the disclosure, the first photo resist layer may be referred to as a photoresist layer, a photo resist, or a resist layer. In some embodiments, the pattern of the first photo resist layer is corresponding to the positioning locations of the conductive patterns/segments of the conductive layer **116a**. In some embodiments, the first photo resist layer may be removed by acceptable ashing process and/or photoresist stripping process, such as using an oxygen plasma or the like, and the disclosure is not limited thereto.

[0028] The first conductive material may be formed in the first openings formed in the first photo resist layer by plating (such as electroplating or electroless plating) or the like. The first conductive material may comprise a metal, such as copper, aluminum, gold, nickel, silver, palladium, tin, or the like. The conductive layer **116a** may be high lead or lead-free. The disclosure is not specifically limited thereto.

[0029] In alternative embodiments, the conductive layer **116a** is formed by, but not limited to, forming a blanket layer of the first conductive material over the seed material layer **114m**; and patterning the first conductive material blanket layer to form the conductive layer **116a** having a plurality of conductive patterns or segments separated from one another. The blanket layer of the first conductive material may be formed by electroplating, deposition, or lamination. The conductive patterns or segments may be formed by using a photolithography and etching process. The etching process may include a dry etching, a wet etching, or a combination thereof. The disclosure is not limited thereto.

[0030] Referring to FIG. 2, in some embodiments, the seed layer material **114m** is patterned to form a seed layer **114a** exposing portions of the dielectric layer **112a**. The seed layer **114a** is disposed between (e.g., in physical contact with) the dielectric layer **112a** and the conductive layer **116a**, for example. In some embodiments, the seed layer material **114m** is patterned by using the conductive layer **116a** as an etching mask to form the seed layer **114a**. For example, the etching process may be a dry etching process, a wet etching process, or a combination thereof; the disclosure is not limited thereto. As shown in FIG. 2, the seed layer **114a** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the dielectric layer **112a**, where portions of the dielectric layer **112a** are not covered by the seed layer **114a**.

[0031] For example, in a vertical projection on the dielectric layer **112a** along the direction Z, the

conductive layer **116a** is completely overlapped with the seed layer **114a**. That is to say, a sidewall of the conductive layer **116a** is substantially aligned with a sidewall of the seed layer **114a**. For example, the conductive layer **116a** and the seed layer **114a** share the same geometrical shape on a top view, e.g., on a X-Y plane. In some embodiments, as shown in FIG. 2, the conductive layer **116a** is physically connected to and electrically connected to the seed layer **114a** respectively underlying thereto. In some embodiments, the conductive layer **116a** and the seed layer **114a** together are referred to as a metallization layer ML1 (or a redistribution layer/line) of the redistribution circuit structure **110**. In some embodiments, the dielectric layer **112a** and the metallization layer ML1 (including the seed layer **114a** and the conductive layer **116a**) are referred to as a first build-up layer of the redistribution circuit structure **110**.

[0032] Referring to FIG. 3, in some embodiments, a dielectric layer **112b**, a seed layer **114b**, a conductive layer **116b**, and a dielectric material layer **118m** are sequentially formed on the structure depicted on FIG. 2. For example, the dielectric layer **112b** is disposed on (e.g., in physical contact with) the first build-up layer of the redistribution circuit structure **110**, and covers an illustrated top surface of the conductive layer **116a**, the illustrated top surface of the dielectric layer **112a** exposing by the conductive layer **116a**, and the sidewalls of the conductive layer **116a** and the seed layer **114a**. In some embodiments, the dielectric layer **112b** has a plurality of openings O1 each exposing a portion of the conductive layer **116a**. As shown in FIG. 3, through the openings O1, a surface TS116a of the conductive layer **116a** is partially exposed for electrically connecting to later-formed connectors, for example. In some embodiments, the dielectric layer **112b** is formed by, but not limited to, forming a blanket layer of dielectric material over the illustrated top surfaces of the conductive layer **116a** and the dielectric layer **112a**, and patterning the dielectric material blanket layer to form the dielectric layer **112b** with a plurality of openings O1 exposing portions of the conductive layer **116a** underneath thereto. The patterning may include a dry etching, a wet etching, or a combination thereof. The formation and material of the dielectric layer **112b** may be the same or similar to the process and material of forming the dielectric layer **112a** as described in FIG. 1, and thus are not repeated therein for brevity. In one embodiment, the material of the dielectric layer **112b** is the same as the material of the dielectric layer **112a**. In an alternative embodiment, the material of the dielectric layer **112b** is different from the material of the dielectric layer **112a**; the disclosure is not limited thereto.

[0033] After the formation of the dielectric layer **112b**, the seed layer **114b** is disposed on (e.g., in physical contact with) the dielectric layer **112b** and extends into openings O1 formed in the dielectric layer **112b** to physically contact the conductive layer **116a** exposed by the openings O1, in some embodiments. In other words, the seed layer **114b** penetrates through the dielectric layer **112b**, and sidewalls of the openings O1 are completely covered by (e.g., lined with) the seed layer **114b**. As shown in FIG. 3, the seed layer **114b** is physically connected to and electrically connected to the conductive layer **116a**, and is electrically coupled to the seed layer **114a** through the conductive layer **116a**, for example. The seed layer **114b** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the dielectric layer **112b**, where portions of the dielectric layer **112b** are not covered by the seed layer **114b**. The formation and material of the seed layer **114b** may be the same or similar to the process and material of forming the seed layer **114a** as described in FIG. 1 through FIG. 2, and thus are not repeated therein for brevity. In one embodiment, the material of the seed layer **114b** is the same as the material of the seed layer **114a**. In an alternative embodiment, the material of the seed layer **114b** is different from the material of the seed layer **114a**; the disclosure is not limited thereto.

[0034] In some embodiments, the conductive layer **116b** is disposed on (e.g., in physical contact with) the seed layer **114b** and over the dielectric layer **112b**. As shown in FIG. 3, the seed layer **114b** may be disposed between the dielectric layer **112b** and the conductive layer **116b** and between the conductive layers **116a** and **116b**. In some embodiments, the conductive layer **116b** is overlapped with the seed layer **114b** in the vertical projection on the dielectric layer **112a** along the

direction Z. That is to say, a sidewall of the seed layer **114b** is substantially aligned with a sidewall of the conductive layer **116b**. In the case, the conductive layer **116b** and the seed layer **114b** share the same geometrical shape on the top view, e.g., the X-Y plane. As shown in FIG. 3, the conductive layer **116b** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the seed layer **114b**. In some embodiments, as shown in FIG. 3, the conductive layer **116b** is physically connected to and electrically connected to the seed layer **114b** respectively underlying thereto. In some embodiments, the conductive layer **116b** and the seed layer **114b** together are referred to as a metallization layer ML2 (or a redistribution layer/line) of the redistribution circuit structure **110**. In some embodiments, the dielectric layer **112b** and the metallization layer ML2 (including the seed layer **114b** and the conductive layer **116b**) are referred to as a second build-up layer of the redistribution circuit structure **110**. [0035] For example, as shown in FIG. 3, the conductive layer **116b** is electrically coupled to the conductive layer **116a** through the seed layer **114b**. In the case, the conductive layer **116b** is electrically coupled to the seed layer **114a** through the seed layer **114b** and the conductive layer **116a**. The formation and material of the conductive layer **116b** may be the same or similar to the process and material of forming the conductive layer **116a** as described in FIG. 1, and thus are not repeated therein for brevity. In one embodiment, the material of the conductive layer **116b** is the same as the material of the conductive layer **116a**. In an alternative embodiment, the material of the conductive layer **116b** is different from the material of the conductive layer **116a**; the disclosure is not limited thereto.

[0036] Continued on FIG. 3, the dielectric material layer **118m** is disposed on (e.g., in physical contact with) the second build-up layer of the redistribution circuit structure **110**, and covers an illustrated top surface of the conductive layer **116b**, the illustrated top surface of the dielectric layer **112b** exposing by the conductive layer **116b**, and the sidewalls of the conductive layer **116b** and the seed layer **114b**. The dielectric layer **112b**, the seed layer **114b**, and the conductive layer **116b** may not be accessibly revealed by the dielectric material layer **118m**, as shown in FIG. 3. In some embodiments, a surface TS**118m** of the dielectric material layer **118m** is considered as a non-planar surface, which adopts an overall topography of the underlying elements (such as the dielectric layer **112b**, the seed layer **114b**, and the conductive layer **116b**). For example, as shown in FIG. 3, a surface roughness R1 of the surface TS**118m**, which is a difference between a surface peak to a surface valley along the direction Z, is greater than or substantially equal to 4 μm . In one embodiment, the surface roughness R1 is ranging about 4 μm to about 7 μm . In an alternative embodiment, the surface roughness R1 is ranging about 4 μm to about 5 μm .

[0037] The formation of the dielectric material layer **118m** may include, but not limited to, conformally forming a blanket of a dielectric material over the second build-up layer of the redistribution circuit structure **110** to completely cover the metallization layer ML2 and the dielectric layer **112b** exposed by the metallization layer ML2. The material of the dielectric material layer **118m** may be PI, PBO, BCB, a nitride such as silicon nitride, an oxide such as silicon oxide, PSG, BSG, BPSG, a combination thereof, or the like. In some embodiments, the dielectric material blanket layer is formed by suitable fabrication techniques such as spin-on coating, CVD, (e.g., PECVD), or the like. In one embodiment, the material of the dielectric material layer **118m** is the same as the material of the dielectric layer **112a** and/or **112b**. For example, the dielectric material layer **118m** is made of PI, while at least one of the dielectric layers **112a** and **112b** is also made of PI. In an alternative embodiment, the material of the dielectric material layer **118m** is different from the material of the dielectric layer **112a** and/or **112b**; the disclosure is not limited thereto. Upon this, the dielectric layers **112a**, **112b** and **118m** and the metallization layer ML1 (including **114a** and **116a**) and ML2 (including **114b** and **116b**) are alternately formed, for example, on the release layer **104** and over the carrier substrate **102**, in accordance with step S11a of FIG. 17.

[0038] Referring to FIG. 4, in some embodiments, the dielectric material layer **118m** is planarized

to form a dielectric layer **118a**, in accordance with step **S12a** of FIG. 17. For example, the dielectric layer **118a** is disposed on (e.g., in physical contact with) the conductive layer **116b**, the seed layer **114b**, and the dielectric layer **112b** exposed by the conductive layer **116b** and the seed layer **114b**. In some embodiments, a surface **TS118a** of the dielectric layer **118a** is considered as a substantially planar surface, which has a surface roughness **R2** (e.g., a difference between a surface peak to a surface valley along the direction **Z**) being less than or substantially equal to 2 μm . In one embodiment, the surface roughness **R2** is ranging about 0.5 μm to about 2 μm . In an alternative embodiment, the surface roughness **R2** is ranging about 1 μm to about 2 μm . In the disclosure, the surface roughness **R2** is in an acceptable tolerance, for example, less than or substantially equal to 2 μm . As the surface roughness **R2** falls within the acceptable tolerance, the surface **TS118a** of the dielectric layer **118a** is substantially flat and planar. As shown in FIG. 4, the surface **TS118a** of the dielectric layer **118a**, for example, provides a high degree of coplanarity and flatness. Due to the high degree of coplanarity and flatness in the surface **TS118a** of the dielectric layer **118a**, the formation of the later-formed layer(s) and/or element(s) is beneficial, such as a process window of a pick-and-place process for a semiconductor die is enlarged.

[0039] In some embodiments, the dielectric material layer **118m** is planarized by a mechanical grinding process, a chemical mechanical polishing (CMP) process, an etching process, or combinations thereof. The etching process may include a dry etching, a wet etching, or a combination thereof. After the planarizing process, a cleaning process may be optionally performed, for example to clean and remove the residue generated from the planarizing process. However, the disclosure is not limited thereto, and the planarizing process may be performed through any other suitable method. As shown in FIG. 4, for example, the dielectric layer **118a** has a thickness **H118a** ranging from about 2 μm to about 30 μm .

[0040] Referring to FIG. 5, in some embodiments, the dielectric layer **118a** is patterned to include a plurality of openings **O2** each exposing a portion of the conductive layer **116b**, in accordance with step **S13a** of FIG. 17. For example, through the openings **O2**, a surface **TS116b** of the conductive layer **116b** is partially exposed for electrically connecting to later-formed connectors, for example. The patterning may include a dry etching, a wet etching, or a combination thereof. As shown in FIG. 5, the surface **TS116b** of the conductive layer **116b** is lower than the surface **TS118a** of the dielectric layer **118a**, in the direction **Z**, for example. In other words, the illustrated top surface (e.g., the surface **TS116b**) of the conductive layer **116b** is partially covered by the dielectric layer **118a**, and the illustrated top surface of the dielectric layer **112b** exposed by the conductive layer **116b** and the seed layer **114b** and the sidewalls of the seed layer **114b** are completely covered by the dielectric layer **118a**. The dielectric layer **118a** may be referred to as a thinned dielectric layer or a capping layer of the redistribution circuit structure **110**.

[0041] In some embodiments, the dielectric layers **112a**, **112b** and **118a** are together referred to as a dielectric structure of the redistribution circuit structure **110**, the metallization layers **ML1** and **ML2** are together referred to as a routing structure of the redistribution circuit structure **110**. If considering the dielectric layers **112a**, **112b** and **118a** are made of the same material, there is no clear interface between any two adjacent layers of the dielectric layers **112a**, **112b** and **118a**. On the other hand, if considering any two adjacent layers of the dielectric layers **112a**, **112b** and **118a** are made of different materials, there is a clear interface between the two adjacent layers of the dielectric layers **112a**, **112b** and **118a**.

[0042] Up to here, the redistribution circuit structure **110** is manufactured. For example, the first build-up layer and the second build-up layer are electrically connected to one another. Although only one first build-up layer and one second build-up layer are included in the redistribution circuit structure **110** as shown in FIG. 5 for illustrative purposes, the number of each of the first and second build-up layers may not be limited to what is depicted in FIG. 5. For example, the number of each of the first and second build-up layers may be one or more than one. The disclosure is not limited thereto.

[0043] Referring to FIG. 6, in some embodiments, at least one conductive pillar **120** and at least one semiconductor die **140** are formed on the redistribution circuit structure **110** and over the carrier substrate **102**. For illustrative purposes, the at least one conductive pillar **120** includes a plurality of conductive pillars **120** (e.g., four conductive pillars **120**), and at least one semiconductor die **140** includes one semiconductor die **140**, as presented in FIG. 6. However, the number of the conductive pillars **120** and the number of the semiconductor die **140** are not limited to what is depicted in the disclosure, and may be selected and designated based on the demand and design requirements. The number of the conductive pillars **120** may be more than or less than four, and the number of the semiconductor die **140** may be more than one. For example, the number of the conductive pillars **120** can be adjusted by changing the number of the openings **O2** formed in the dielectric layer **118a**. In some embodiments, the conductive pillars **120** and the semiconductor die **140** are arranged side-by-side on a side (e.g., the surface **TS118a**) of the redistribution circuit structure **110**.

[0044] In some embodiments, the conductive pillars **120** are disposed on the redistribution circuit structure **110** and extend into the openings **O2** to physically connect to and electrically connect to the metallization layer **ML2** of the redistribution circuit structure **110**, in accordance with step **S20** of FIG. 16. As shown in FIG. 6, the conductive pillars **120** are in physical contact with the conductive layer **116b** through the openings **O2** formed in the dielectric layer **118a**, for example. In some embodiments, the conductive pillars **120** each include a seed pattern **122** and a conductive via **124** standing thereon. As shown in FIG. 6, the seed patterns **122** may be disposed on the surface **TS118a** of the dielectric layer **118a** and further extended into the openings **O2**, and the conductive vias **124** may be respectively disposed on (e.g., in physical contact with) the seed patterns **122**. In the case, the seed patterns **122** penetrate through the dielectric layer **118a**, and sidewalls of the openings **O2** are completely covered by (e.g., lined with) the seed patterns **122**. In other words, the conductive pillars **120** penetrate through the dielectric layer **118a**, where the conductive vias **124** are electrically coupled to the conductive layer **116b** through the seed patterns **122**.

[0045] The formation and material of the seed patterns **122** may be the same or similar to the process and material of forming the seed layer **114a** as described in FIG. 1 through FIG. 2, and the formation and material of the conductive vias **124** may be the same or similar to the process and material of forming the conductive layer **116a** as described in FIG. 1; thus, are not repeated therein for brevity. In some embodiments, a material of the conductive vias **124** may include a metal material such as copper or copper alloys, or the like. As shown in FIG. 6, for example, in the vertical projection on the dielectric layer **112a** along the direction **Z**, the conductive vias **124** are completely overlapped with the seed patterns **122**. That is to say, a sidewall of one conductive via **124** may be substantially aligned with a sidewall of a respective one seed pattern **122**. For example, one conductive via **124** and the respective one seed pattern **122** share the same geometrical shape on the top view, e.g., the X-Y plane. In some embodiments, the conductive pillars **120** may be through integrated fan-out (InFO) vias, vertical connectors, or vertical connections. In some embodiments, the conductive pillars **120** are arranged along but not on a cutting line (not shown) between two package structures (e.g., two of the package structures **100a**).

[0046] Continued on FIG. 6, in some embodiments, the semiconductor die **140** is disposed on the redistribution circuit structure **110** and next to the conductive pillars **120**, in accordance with step **S30** of FIG. 16. In some embodiments, the semiconductor die **140** is picked and placed over the redistribution circuit structure **110** and disposed on the surface **TS118a** of the dielectric layer **118a**, where the semiconductor die **140** is laterally distant from the conductive pillars **120**. In some embodiments, the semiconductor die **140** includes a semiconductor substrate **141** having an active surface **141t** and a backside surface **141b** opposite to the active surface **141t**, a plurality of pads **142** distributed on the active surface **141t**, a passivation layer **143** covering the active surface **141t** and a portion of the pads **142**, a post passivation layer **144** covering the passivation layer **143** and a portion of the pads **142**, a plurality of conductive vias **145** connecting to the pads **142** exposing by

the passivation layer **143** and the post passivation layer **144**, and a protection layer **146** disposed on and covering the post passivation layer **144** and the conductive vias **145**. The pads **142**, the passivation layer **143**, the post passivation layer **144**, the conductive vias **145**, and the protection layer **146** may be formed on the semiconductor substrate **141**. In some embodiments, the pads **142** are partially exposed by the passivation layer **143** and the post passivation layer **144**, the conductive vias **145** are respectively disposed on and electrically connected to the pads **142**, and the protection layer **146** covers the post passivation layer **144** exposed by the conductive vias **145** and illustrated top surfaces (not labeled) of the conductive vias **145** for providing protection, which avoids the conductive vias **145** of the semiconductor die **140** are damaged during the transportation process or the pick-and-place process.

[0047] However, the disclosure may not be limited thereto. Alternatively, the illustrated top surfaces of the conductive vias **145** may be accessibly exposed by the protection layer **146**. Or alternatively, the post passivation layer **144** and/or the protection layer **146** may be omitted.

[0048] In other embodiments, the conductive vias **145** and the protection layer **146** are omitted. For example, the semiconductor die **140** includes the semiconductor substrate **141** having the active surface **141t** and the backside surface **141b** opposite to the active surface **141t**, the plurality of pads **142** distributed on the active surface **141t**, the passivation layer **143** covering the active surface **141t** and a portion of the pads **142**, and the post passivation layer **144** covering the passivation layer **143** and a portion of the pads **142**. Alternatively, the post passivation layer **144** may be omitted.

[0049] The material of the semiconductor substrate **141** may include a silicon substrate including active components (e.g., transistors, memories (such as N-type metal-oxide semiconductor (NMOS), P-type metal-oxide semiconductor (PMOS) devices, a combination thereof, or the like), a combination thereof, or the like) and/or passive components (e.g., resistors, capacitors, inductors, combinations thereof, or the like) formed therein or thereon. In some embodiments, such active components and passive components are formed in a front-end-of-line (FEOL) process. The semiconductor substrate **141** may be a bulk silicon substrate, such as a bulk substrate of monocrystalline silicon, a doped silicon substrate, an undoped silicon substrate, or a silicon-on-insulator (SOI) substrate, where the dopant of the doped silicon substrate may be an N-type dopant, a P-type dopant, or a combination thereof. The disclosure is not limited thereto.

[0050] Furthermore, the semiconductor substrate **141** may further include an interconnection structure or interconnect (not shown) disposed on the active surface **141t**. The interconnection structure may include one or more inter-dielectric layers and one or more patterned conductive layers stacked alternately for providing routing function to the active components and the passive components embedded in or formed on the semiconductor substrate **141**, where the pads **142** may be referred to as an outermost layer of the patterned conductive layers of the interconnection structure. In some embodiment, the interconnection structure is formed in a back-end-of-line (BEOL) process. The inter-dielectric layers may be silicon oxide layers, silicon nitride layers, silicon oxy-nitride layers, or dielectric layers formed by other suitable dielectric materials, and the inter-dielectric layers may be formed by deposition or the like. The patterned conductive layers may be patterned copper layers or other suitable patterned metal layers, and the patterned conductive layers may be formed by electroplating or deposition. However, the disclosure is not limited thereto.

[0051] The pads **142** are aluminum pads or other suitable metal pads, for example. The conductive vias **145** are copper pillars, copper alloy pillar or other suitable metal pillars containing copper metal, for example. In some embodiments, the passivation layer **143**, the post passivation layer **144**, and the protection layer **146** may be a PBO layer, a PI layer, or other suitable polymers. In some alternative embodiments, the passivation layer **143**, the post passivation layer **144**, and the protection layer **146** may be made of inorganic materials, such as silicon oxide, silicon nitride, silicon oxynitride, or any suitable dielectric material. The material of the passivation layer **143**, the

material of the passivation layer **143**, and the material of the protection layer **146** may be the same. Alternatively, the material of the passivation layer **143**, the material of the passivation layer **143**, and the material of the protection layer **146** may be different, in part or all. For example, the passivation layer **143** and the protection layer **146** independently are a silicon oxide layer, a silicon nitride layer, a silicon oxy-nitride layer, or a dielectric layer formed by other suitable dielectric materials, and the post-passivation layer **144** is a PI layer, a PBO layer, or a dielectric layer formed by other suitable polymers.

[0052] It is noted that, the semiconductor die **140** described herein is referred as a semiconductor chip or an integrated circuit (IC), for example. In an alternative embodiment, the semiconductor die **140** described herein may be a semiconductor device. In some embodiments, the semiconductor die **140** includes a digital chip, an analog chip, or a mixed signal chip. In some embodiments, the semiconductor die **140** is a logic die such as a central processing unit (CPU), a graphics processing unit (GPU), a neural network processing unit (NPU), a deep learning processing unit (DPU), a tensor processing unit (TPU), a system-on-a-chip (SoC), an application processor (AP), and a microcontroller; a power management die such as a power management integrated circuit (PMIC) die; a wireless and radio frequency (RF) die; a baseband (BB) die; a sensor die such as a photo/image sensor chip; a micro-electro-mechanical-system (MEMS) die; a signal processing die such as a digital signal processing (DSP) die; a front-end die such as an analog front-end (AFE) dies; an application-specific die such as an application-specific integrated circuit (ASIC), a field-programmable gate array (FPGA); a combination thereof; or the like. In alternative embodiments, the semiconductor die **140** is a memory die with a controller or without a controller, where the memory die includes a single-form die such as a dynamic random access memory (DRAM) die, a static random access memory (SRAM) die, a resistive random-access memory (RRAM) die, a magnetoresistive random-access memory (MRAM) die, a NAND flash memory, a wide I/O memory (WIO); a pre-stacked memory cube such as a hybrid memory cube (HMC) module, a high bandwidth memory (HBM) module; a combination thereof; or the like. In further alternative embodiments, the semiconductor die **140** is an artificial intelligence (AI) engine such as an AI accelerator; a computing system such as an AI server, a high-performance computing (HPC) system, a high-power computing device, a cloud computing system, a networking system, an edge computing system, an immersive memory computing system (ImMC), a system-on-integrated-circuit (SoIC) system, etc.; a combination thereof; or the like. In some other embodiments, the semiconductor die **140** is an electrical and/or optical input/output (I/O) interface die, an integrated passives die (IPD), a voltage regulator (VR) die, a local silicon interconnect (LSI) die with or without deep trench capacitor (DTC) features, a LSI die with multi-tier functions such as electrical and/or optical network circuit interfaces, IPD, VR, DTC, or the like. Alternatively, the semiconductor die **140** may be referred to as a chip or an IC of combination-type, such as a WiFi chip simultaneously including both of a RF chip and a digital chip. The type of the semiconductor die **140** may be selected and designated based on the demand and design requirements, and thus is not specifically limited in the disclosure.

[0053] In certain embodiments, additional semiconductor die(s) of the same type or different types may be included. The additional semiconductor die(s) may include digital chips, analog chips, or mixed signal chips, such as ASIC chips, sensor chips, wireless and RF chips, memory chips, logic chips, voltage regulator chips, or the like. The disclosure is not limited thereto. It should be appreciated that the illustration of the semiconductor die **140** and its components throughout all figures is schematic and is not in scale.

[0054] As illustrated in FIG. **6**, in some embodiments, the semiconductor die **140** is bonded to the redistribution circuit structure **110** by adhering onto the redistribution circuit structure **110** with a connecting film **130**. The semiconductor die **140** (e.g., the backside surface **141b** thereof) may be adhered to the surface **TS118a** of the dielectric layer **118a** of the redistribution circuit structure **110** by the connecting film **130**. For example, as shown in FIG. **6**, the connecting film **130** is

sandwiched between the semiconductor die **140** and the redistribution circuit structure **110**. Owing to the connecting film **130**, the semiconductor die **140** is stably adhered to the dielectric layer **118a** of the redistribution circuit structure **110**. Owing to the dielectric layer **118a** (having the surface **TS118a** with high degree of coplanarity and flatness), there is no or little air or void trapped between the connecting film **130** and the redistribution circuit structure **110**, thereby an undesired movement of the semiconductor die **140** and/or an insulating encapsulation **150** (see FIG. 7 through FIG. 8) surrounding the semiconductor die **140** and/or the moisture trapped by the void and/or the risk of “pop-corn” may be suppressed, which enhancing the reliability and performance of the package structure **100a**.

[0055] In some embodiments, the connecting film **130** includes a thermally conductive die attach film, which is a layer made of adhesives (for example, a polymer-based adhesive such as example, epoxy-based resin, silicon-based resin, rubber-based resin, acrylic polymer, or the like), other suitable insulating material, or the like, with thermally conductive fillers filled therein. In some embodiments, a material of the thermally conductive fillers includes metal or metal alloy. In alternative embodiments, the material of the thermally conductive fillers includes boron nitride or the like. In the case, an amount of the thermally conductive filler (by weight percentage) presented in the thermally conductive die attach film is ranging from about 40% to about 95%, such as from about 50% to about 80%. Alternatively, the connecting film **130** includes a thermally conductive die attach film, which is a layer made of graphite, graphene, or the like. In some embodiments, if considering the connecting film **130** is a thermally conductive die attach film, the connecting film **130** has a thermal conductivity being about 0.5 W/(m.Math.K) to about 50 W/(m.Math.K), such as about 2 W/(m.Math.K). However, the disclosure is not limited thereto.

[0056] In other embodiments, the connecting film **130** includes a non-thermally conductive die attach film, which is a layer made of adhesives (for example, a polymer-based adhesive such as example, epoxy-based resin, silicon-based resin, rubber-based resin, acrylic polymer, or the like), other suitable insulating material, or the like. In the case, the non-thermally conductive die attach film may be with or without non-thermally conductive fillers filled therein. In some embodiments, the non-thermally conductive fillers include silica, alumina, or the like. In the embodiments of which the non-thermally conductive die attach film includes the non-thermally conductive fillers, an amount of the non-thermally conductive filler (by weight percentage) presented in the non-thermally conductive die attach film is ranging from about 5% to about 50%. In some embodiments, if considering the connecting film **130** is a non-thermally conductive die attach film, the connecting film **130** has a thermal conductivity less than about 0.2 W/(m.Math.K).

[0057] In some embodiments, a thickness **H130** of the connecting film **130** is ranging from about 5 μm to about 200 μm . In the embodiments of which the connecting film **130** is the thermally conductive die attach film, the connecting film **130** thermally couples the semiconductor die **140** and the redistribution circuit structure **110**, which helps to dissipate heat from the semiconductor die **140**; thus, the thickness **H130** of the connecting film **130** can be thick to ensure a high surface coverage capability. In the embodiments of which the connecting film **130** is the non-thermally conductive die attach film, in order to allow the connecting film **130** being capable of thermally coupling the semiconductor die **140** and the redistribution circuit structure **110** for the heat dissipation of the semiconductor die **140**, the thickness **H130** of the connecting film **130** can be thin. In other words, the heat dissipation of the package structure **100a** may be controlled (e.g., to be improved or maintained based on the demand and design requirements) by adjusting the thermal conductivity and/or the thickness **H130** of the connecting film **130**, for example, in the disclosure.

[0058] In FIG. 6, for example, the semiconductor die **140** and the conductive pillars **120** are arranged next to each other along the X-Y plane. In some embodiments, the semiconductor die **140** are not overlapped with the conductive pillars **120** in the direction Z, but are overlapped with each other in the direction X and/or the direction Y. In one embodiment, a height of the conductive pillars **120** is greater than a height of the semiconductor die **140**, as shown in FIG. 6. Alternatively,

the height of the conductive pillars **120** may be less than or substantially equal to the height of the semiconductor die **140**.

[0059] Referring to FIG. 7, in some embodiments, an encapsulation material **150m** is formed on the redistribution circuit structure **110** to encapsulate the conductive pillars **120** and the semiconductor die **140**, in accordance with step S40 of FIG. 16. The conductive pillars **120** and the semiconductor die **140** are embedded in the encapsulation material **150m**, and the redistribution circuit structure **110** exposed by the conductive pillars **120** and the semiconductor die **140** is covered by the encapsulation material **150m**, for example. In other words, the conductive pillars **120** and the protection layer **146** of the semiconductor die **140** may be not accessibly revealed and are well-protected by the encapsulation material **150m**. In some embodiments, the encapsulation material **150m** is a molding compound, a molding underfill, a resin (such as epoxy-based resin), or the like. The encapsulation material **150m** may be formed by a molding process, such as a compression molding process or a transfer molding process. In some embodiments, the encapsulation material **150m** may further include inorganic filler or inorganic compound (e.g., silica, clay, and so on) which can be added therein to optimize coefficient of thermal expansion (CTE) of the encapsulation material **150m**. The disclosure is not limited thereto.

[0060] Referring to FIG. 7 and FIG. 8, in some embodiments, the encapsulation material **150m** are planarized to form an insulating encapsulation **150** exposing the conductive pillars **120** and the semiconductor die **140**, in accordance with step S40 of FIG. 16. The insulating encapsulation **150** is disposed over the redistribution circuit structure **110** to laterally encapsulate the semiconductor die **140** and the conductive pillars **120**, for example, as shown in FIG. 8. In some embodiments, the encapsulation material **150m** is planarized by a mechanical grinding process and/or a CMP process. In some embodiments, during the planarizing process of the encapsulation material **150m**, the protection layer **146** is planarized to accessibly reveal the conductive vias **145**. In some embodiments, portions of the conductive vias **145** and portions of the conductive pillars **120** are slightly planarized as well. As shown in FIG. 8, a surface TS150 of the insulating encapsulation **150** is substantially leveled with surfaces TS145 of the conductive vias **145** and a surface TS146 of the protection layer **146** of the semiconductor die **140** and surfaces TS120 of the conductive pillars **120**, for example. In some embodiments, the surface TS150 of the insulating encapsulation **150**, the surfaces TS120 of the conductive pillars **120**, and the surfaces TS145 of the conductive vias **145** and the surface TS146 of the protection layer **146** of the semiconductor die **140** are substantially coplanar to each other. The surfaces TS145 of the conductive vias **145** and the surface TS146 of the protection layer **146** together may be referred to as a front side (or an active side) TS140 of the semiconductor die **140**, and the backside surface **141b** may be referred to as a rear side (or a non-active side) BS140 of the semiconductor die **140**. For example, in direction Z, the front side TS140 of the semiconductor die **140** is opposite to the rear side BS140 of the semiconductor die **140**.

[0061] In some embodiments, the exposed portion of the conductive vias **145** is located on the front side TS140 of the semiconductor die **140**, and the connecting film **130** is located on the rear side BS140 of the semiconductor die **140**. The insulating encapsulation **150** encapsulates sidewalls of the semiconductor die **140** and sidewalls of the conductive pillars **120**, and the insulating encapsulation **150** is penetrated by the conductive pillars **120**. In some embodiments, after the planarizing process, a cleaning step may be optionally performed to clean and remove the residue generated from the planarizing process. As show in FIG. 8, a thickness H150 of the insulating encapsulation **150** is substantially equal to a sum of the thickness H130 of the connecting film **130** and a thickness H140 of the semiconductor die **140**, for example. In the case, sidewalls of the connecting film **130** is completely covered (e.g., in physical contact with) the insulating encapsulation **150**.

[0062] Referring to FIG. 9, in some embodiments, a redistribution circuit structure **160** is formed on the insulating encapsulation **150**, the semiconductor die **140**, and the conductive pillars **120**, in accordance with step S50 of FIG. 16. In some embodiments, the redistribution circuit structure **160**

includes at least one dielectric layer **162** (e.g., **162a**, **162b**, and **162c**), at least one seed layer **164** (e.g., **164a**, **164b**, and **164c**), at least one conductive layer **166** (e.g., **166a**, **166b**, and **166c**), and a dielectric layer **168**. However, in the disclosure, the numbers of layers of the dielectric layer **162**, the seed layer **164**, and the conductive layer **166** are not limited to what is depicted in FIG. 9, where the numbers of the layers of the dielectric layer **162**, the seed layer **164**, and the conductive layer **166** may be one or more than one depending upon the demand and design requirements. In some embodiments, one conductive layer **166** includes a line portion extending along a horizontal direction (e.g., the direction X or the direction Y), a via portion extending along a vertical direction (e.g., the direction Z) connecting to the line portion, or a combination thereof.

[0063] In some embodiments, a dielectric layer **162a**, a seed layer **164a**, and a conductive layer **166a** are sequentially formed over the insulating encapsulation **150**. As shown in FIG. 9, for example, the dielectric layer **162a** is disposed on (e.g., in physical contact with) the insulating encapsulation **150**, the semiconductor die **140**, and the conductive pillars **120**. In some embodiments, the dielectric layer **162a** has a plurality of openings **O3** each exposing portions of the conductive pillars **120** and portions of the conductive vias **145** of the semiconductor die **140**. As shown in FIG. 9, through the openings **O3**, the surfaces **TS120** of the conductive pillars **120** and the surfaces **TS145** of the conductive vias **145** are partially exposed for electrically connecting to later-formed connectors, for example.

[0064] In some embodiments, the seed layer **164a** is disposed on (e.g., in physical contact with) the dielectric layer **162a** and extends into openings **O3** formed in the dielectric layer **162a** to physically contact the conductive pillars **120** and the conductive vias **145** exposed by the openings **O3**. In other words, the seed layer **164a** penetrates through the dielectric layer **162a**, and sidewalls of the openings **O3** are completely covered by (e.g., lined with) the seed layer **164a**. As shown in FIG. 9, the seed layer **164a** is physically connected to and electrically connected to the conductive pillars **120** and the conductive vias **145**, and is electrically coupled to the redistribution circuit structure **110** through the conductive pillars **120** and electrically coupled to the semiconductor die **140** through the conductive vias **145**, for example. The seed layer **164a** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the dielectric layer **162a**, where portions of the dielectric layer **162a** are not covered by the seed layer **164a**, as shown in FIG. 9.

[0065] In some embodiments, the conductive layer **166a** is disposed on (e.g., in physical contact with) the seed layer **164a** and over the dielectric layer **162a**. As shown in FIG. 9, the seed layer **164a** may be disposed between the dielectric layer **162a** and the conductive layer **166a**, between the conductive pillars **120** and the conductive layer **166a**, and between the conductive vias **145** and the conductive layer **166a**. In some embodiments, the conductive layer **166a** is overlapped with the seed layer **164a** in a vertical projection on the dielectric layer **162a** along the direction Z. That is to say, a sidewall of the seed layer **164a** is substantially aligned with a sidewall of the conductive layer **166a**. In the case, the conductive layer **166a** and the seed layer **164a** share the same geometrical shape on the top view, e.g., the X-Y plane. As shown in FIG. 9, the conductive layer **166a** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the seed layer **164a**. In some embodiments, as shown in FIG. 9, the conductive layer **166a** is physically connected to and electrically connected to the seed layer **164a** respectively underlying thereto. In some embodiments, the conductive layer **166a** and the seed layer **164a** together are referred to as a metallization layer **ML3** (or a redistribution layer/line) of the redistribution circuit structure **160**. In some embodiments, the dielectric layer **162a** and the metallization layer **ML3** (including the seed layer **164a** and the conductive layer **166a**) are referred to as a first build-up layer of the redistribution circuit structure **160**. For example, the conductive layer **166a** is electrically coupled to the conductive pillars **120** and the conductive vias **145** through the seed layer **164a**. In the case, the conductive layer **166a** is electrically coupled to the redistribution circuit structure **110** through the conductive pillars **120** and the seed layer **164a**.

[0066] Continued on FIG. 9, in some embodiments, a dielectric layer **162b**, a seed layer **164b**, and a conductive layer **166b** are sequentially formed over the first build-up layer of the redistribution circuit structure **160**. For example, the dielectric layer **162b** is disposed on (e.g., in physical contact with) the metallization layer **ML3** and the dielectric layer **162a** exposed by the metallization layer **ML3**. In some embodiments, the dielectric layer **162b** has a plurality of openings **O4** each exposing portions of the conductive layer **166a**. As shown in FIG. 9, through the openings **O4**, a surface **TS166a** of the conductive layer **166a** is partially exposed for electrically connecting to later-formed connectors, for example.

[0067] In some embodiments, the seed layer **164b** is disposed on (e.g., in physical contact with) the dielectric layer **162b** and extends into openings **O4** formed in the dielectric layer **162b** to physically contact the conductive layer **166a** exposed by the openings **O4**. In other words, the seed layer **164b** penetrates through the dielectric layer **162b**, and sidewalls of the openings **O4** are completely covered by (e.g., lined with) the seed layer **164b**. As shown in FIG. 9, the seed layer **164b** is physically connected to and electrically connected to the conductive layer **166a**, and is electrically coupled to the seed layer **164a** through the conductive layer **166a**, for example. The seed layer **164b** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the dielectric layer **162b**, where portions of the dielectric layer **162b** are not covered by the seed layer **164b**, as shown in FIG. 9.

[0068] In some embodiments, the conductive layer **166b** is disposed on (e.g., in physical contact with) the seed layer **164b** and over the dielectric layer **162b**. As shown in FIG. 9, the seed layer **164b** may be disposed between the dielectric layer **162b** and the conductive layer **166b** and between the conductive layers **166a** and **166b**. In some embodiments, the conductive layer **166b** is overlapped with the seed layer **164b** in the vertical projection on the dielectric layer **162a** along the direction **Z**. That is to say, a sidewall of the seed layer **164b** is substantially aligned with a sidewall of the conductive layer **166b**. In the case, the conductive layer **166b** and the seed layer **164b** share the same geometrical shape on the top view, e.g., the **X-Y** plane. As shown in FIG. 9, the conductive layer **166b** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the seed layer **164b**. In some embodiments, as shown in FIG. 9, the conductive layer **166b** is physically connected to and electrically connected to the seed layer **164b** respectively underlying thereto. In some embodiments, the conductive layer **166b** and the seed layer **164b** together are referred to as a metallization layer **ML4** (or a redistribution layer/line) of the redistribution circuit structure **160**. In some embodiments, the dielectric layer **162b** and the metallization layer **ML4** (including the seed layer **164b** and the conductive layer **166b**) are referred to as a second build-up layer of the redistribution circuit structure **160**. For example, the conductive layer **166b** is electrically coupled to the conductive layer **166a** through the seed layer **164b**.

[0069] Continued on FIG. 9, in some embodiments, a dielectric layer **162c**, a seed layer **164c**, and a conductive layer **166c** are sequentially formed over the second build-up layer of the redistribution circuit structure **160**. For example, the dielectric layer **162c** is disposed on (e.g., in physical contact with) the metallization layer **ML4** and the dielectric layer **162b** exposed by the metallization layer **ML4**. In some embodiments, the dielectric layer **162c** has a plurality of openings **O5** each exposing portions of the conductive layer **166b**. As shown in FIG. 9, through the openings **O5**, a surface **TS166b** of the conductive layer **166b** is partially exposed for electrically connecting to later-formed connectors, for example.

[0070] In some embodiments, the seed layer **164c** is disposed on (e.g., in physical contact with) the dielectric layer **162c** and extends into openings **O5** formed in the dielectric layer **162c** to physically contact the conductive layer **166b** exposed by the openings **O5**. In other words, the seed layer **164c** penetrates through the dielectric layer **162c**, and sidewalls of the openings **O5** are completely covered by (e.g., lined with) the seed layer **164c**. As shown in FIG. 9, the seed layer **164c** is physically connected to and electrically connected to the conductive layer **166b**, and is electrically

coupled to the seed layer **164b** through the conductive layer **166b**, for example. The seed layer **164c** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the dielectric layer **162c**, where portions of the dielectric layer **162c** are not covered by the seed layer **164c**, as shown in FIG. 9.

[0071] In some embodiments, the conductive layer **166c** is disposed on (e.g., in physical contact with) the seed layer **164c** and over the dielectric layer **162c**. As shown in FIG. 9, the seed layer **164c** may be disposed between the dielectric layer **162c** and the conductive layer **166c** and between the conductive layers **166b** and **166c**. In some embodiments, the conductive layer **166c** is overlapped with the seed layer **164c** in the vertical projection on the dielectric layer **162a** along the direction Z. That is to say, a sidewall of the seed layer **164c** is substantially aligned with a sidewall of the conductive layer **166c**. In the case, the conductive layer **166c** and the seed layer **164c** share the same geometrical shape on the top view, e.g., the X-Y plane. As shown in FIG. 9, the conductive layer **166c** may include a plurality of conductive patterns/segments (not labeled, which are separated from one another) disposed on the seed layer **164c**. In some embodiments, as shown in FIG. 9, the conductive layer **166c** is physically connected to and electrically connected to the seed layer **164c** respectively underlying thereto. In some embodiments, the conductive layer **166c** and the seed layer **164c** together are referred to as a metallization layer ML5 (or a redistribution layer/line) of the redistribution circuit structure **160**. In some embodiments, the dielectric layer **162c** and the metallization layer ML5 (including the seed layer **164c** and the conductive layer **166c**) are referred to as a third build-up layer of the redistribution circuit structure **160**. For example, the conductive layer **166c** is electrically coupled to the conductive layer **166b** through the seed layer **164c**.

[0072] Thereafter, the dielectric layer **168** is formed on the third build-up layer of the redistribution circuit structure **160**, in some embodiment. For example, the dielectric layer **168** is disposed on (e.g., in physical contact with) the metallization layer ML5 and the dielectric layer **162c** exposed by the metallization layer ML5. In some embodiments, the dielectric layer **168** has a plurality of openings O6 each exposing portions of the conductive layer **166c**. As show in FIG. 9, through the openings O6, a surface TS166c of the conductive layer **166c** is partially exposed for electrically connecting to later-formed connectors, for example. The dielectric layer **168** may be referred to as a capping layer of the redistribution circuit structure **160**.

[0073] In some embodiments, the dielectric layers **162a**, **162b**, **162c** and **168** are together referred to as a dielectric structure of the redistribution circuit structure **160**, the metallization layers ML3, ML4, ML5 are together referred to as a routing structure of the redistribution circuit structure **160**. If considering the dielectric layers **162a**, **162b**, **162c** and **168** are made of the same material, there is no clear interface between any two adjacent layers of the dielectric layers **162a**, **162b**, **162c** and **168**. On the other hand, if considering any two adjacent layers of the dielectric layers **162a**, **162b**, **162c** and **168** are made of different materials, there is a clear interface between the two adjacent layers of the dielectric layers **162a**, **162b**, **162c** and **168**.

[0074] Up to here, the redistribution circuit structure **160** is manufactured. In some embodiments, the first, second, and third build-up layers are electrically connected to one another. The redistribution circuit structure **160** may be disposed on and electrically connected to the conductive pillars **120** and the semiconductor die **140**, as shown in FIG. 9. Although only one first build-up layer, one second build-up layer, and one third build-up layer are included in the redistribution circuit structure **160** as shown in FIG. 9 for illustrative purposes, the number of each of the first, second, and third build-up layers may not be limited to what is depicted in FIG. 9. For example, the number of each of the first, second, and third build-up layers may be one or more than one depending on the demand and design requirements; the disclosure is not limited thereto. As shown in FIG. 9, the redistribution circuit structure **160** may be referred to as a front-side redistribution circuit structure or layer of the semiconductor die **140**, while the redistribution circuit structure **110** may be referred to as a back-side redistribution circuit structure or layer of the semiconductor die

140. In some embodiments, the redistribution circuit structure **110** is electrically coupled to the semiconductor die **140** through the conductive pillars **120** and the redistribution circuit structure **160**.

[0075] The formations and materials of the dielectric layers **162a**, **162b**, **162c**, and **168** may be the same or similar to the process and material of forming the dielectric layer **112a** and/or **112b** as described in FIG. 1 through FIG. 3, and thus are not repeated therein for brevity. In one embodiment, the materials of the dielectric layers **162a**, **162b**, **162c**, and **168** are the same as the material of the dielectric layer **112a** and/or **112b**. In an alternative embodiment, the materials of the dielectric layers **162a**, **162b**, **162c**, and **168** independently are different from the material of the dielectric layer **112a** and/or **112b**; the disclosure is not limited thereto. The formations and materials of the seed layers **164a**, **164b** and **164c** may be the same or similar to the process and material of forming the seed layer **114a** and/or **114b** as described in FIG. 1 thorough FIG. 3, and thus are not repeated therein for brevity. In one embodiment, the materials of the seed layers **164a**, **164b** and **164c** are the same as the material of the seed layer **114a** and/or **114b**. In an alternative embodiment, the materials of the seed layers **164a**, **164b** and **164c** independently are different from the material of the seed layer **114a** and/or **114b**; the disclosure is not limited thereto. The formations and materials of the conductive layers **166a**, **166b**, and **166c** may be the same or similar to the process and material of forming the conductive layer **116a** and/or **166b** as described in FIG. 1 through FIG. 3, and thus are not repeated therein for brevity. In one embodiment, the materials of the conductive layers **166a**, **166b**, and **166c** are the same as the material of the conductive layer **116a** and/or **116b**. In an alternative embodiment, the materials of the conductive layers **166a**, **166b**, and **166c** independently are different from the material of the conductive layer **116a** and/or **116b**; the disclosure is not limited thereto.

[0076] Referring to FIG. 10, in some embodiments, a plurality of under-ball metallurgy (UBM) patterns **172** and a plurality of conductive terminals **174** are sequentially formed over the redistribution circuit structure **160**, in accordance with step S60 of FIG. 16. In some embodiments, the UBM patterns **172** each are located between a respective one of the conductive terminals **174** and the dielectric layer **168** of the redistribution circuit structure **160**. Due to the UBM patterns **172**, the adhesion strength between the conductive terminals **174** and the dielectric layer **168** of the redistribution circuit structure **160** is enhanced. In some embodiments, the conductive terminals **174** are electrically coupled to the redistribution circuit structure **160** through the UBM patterns **172**. In some embodiments, some of the conductive terminals **174** are electrically coupled to the semiconductor die **140** through some of the UBM patterns **172** and the redistribution circuit structure **160**. In some embodiments, some of the conductive terminals **174** are electrically coupled to the conductive pillars **120** through some of the UBM patterns **172** and the redistribution circuit structure **160**. In some embodiments, some of the conductive terminals **174** are electrically coupled to the redistribution circuit structure **110** through some of the UBM patterns **172**, the redistribution circuit structure **160**, and the conductive pillars **120**.

[0077] In some embodiments, the UBM patterns **172** are disposed on (e.g., in physical contact with) the conductive layer **166c** exposed by the openings O6 formed in the dielectric layer **168**. As shown in FIG. 10, in some embodiments, the UBM patterns **172** are physically connected to and electrically connected to the redistribution circuit structure **160**. In some embodiments, the UBM patterns **172** are made of a metal layer including a single layer or a metallization layer including a composite layer with a plurality of sub-layers formed of different materials. In some embodiments, the UBM patterns **172** include copper, nickel, molybdenum, titanium, tungsten, titanium nitride, titanium tungsten, combinations thereof, or the like. The UBM patterns **172** may include a titanium layer and a copper layer over the titanium layer. The UBM patterns **172** may be formed using, for example, electroplating, sputtering, PVD, or the like. For example, the UBM patterns **172** are conformally formed on the dielectric layer **168** by sputtering to extend on an outermost surface of the dielectric layer **168** and further extend into the openings O6 formed in the dielectric layer **168**,

and thus are in physical contact with the surface TS166c of the conductive layer 166c exposed by the openings O6 formed in the dielectric layer 168. The UBM patterns 172 are electrically isolated from one another. The number of the UBM patterns 172 may not be limited in this disclosure, and may correspond to the number of the portions of the conductive layer 166c exposed by the openings O6 formed in the dielectric layer 168.

[0078] As shown in FIG. 10, in some embodiments, the conductive terminals 174 are physically connected to and electrically connected to the UBM patterns 172, and are electrically coupled to the redistribution circuit structure 160 through the UBM patterns 172. In some embodiments, the conductive terminals 174 are disposed on the UBM patterns 172 by ball placement process or reflow process. The conductive terminals 174 are, for example, solder balls or ball grid array (BGA) balls or bumps. Alternatively, the conductive terminals 174 may include micro-bumps, metal pillars, electroless nickel-electroless palladium-immersion gold (ENEPIG) formed bumps, controlled collapse chip connection (C4) bumps, or the like; and may be formed by plating. The conductive terminals 174 may be solder free. The number of the conductive terminals 174 may not be limited to the disclosure, and may be designated and selected based on the number of the UBM patterns 172.

[0079] However, the disclosure is not limited thereto. In some alternative embodiments, the UBM patterns 172 may be omitted. In such alternative embodiments, the conductive terminals 174 may be directly connected to (e.g., in physical contact with) the redistribution circuit structure 160 (e.g., the portions of the conductive layer 166c exposed by the openings O6). The conductive terminals 174 may be referred to as conductors or conductive connectors, in the disclosure.

[0080] Referring to FIG. 11, in some embodiments, the whole structure depicted in FIG. 10 along with the carrier substrate 102 is flipped (turned upside down), where the conductive terminals 174 are placed to a holding device HD, and the carrier substrate 102 is then debonded from the dielectric layer 112a. In some embodiments, the holding device HD may be an adhesive tape, a carrier film or a suction pad being supported by a frame. The disclosure is not limited thereto. In some embodiments, the dielectric layer 112a is easily separated from the carrier substrate 102 due to the release layer 104. In some embodiments, the carrier substrate 102 is detached from the dielectric layer 112a through a debonding process, where the carrier substrate 102 and the release layer 104 are debonded and then removed. In some embodiments, after the deboning, a surface BS112a of the dielectric layer 112a is exposed, as show in FIG. 11. In one embodiment, the debonding process is a laser debonding process. During the debonding step, the holding device HD is used to secure the structure depicted in FIG. 10 before debonding the carrier substrate 102 and the release layer 104.

[0081] Referring to FIG. 12, in some embodiments, the dielectric layer 112a is patterned to include a plurality of openings O7 formed therethrough and each exposing a portion of the seed layer 114a. As show in FIG. 12, through the openings O7, a surface BS114a of the seed layer 114a is partially exposed for electrically connecting to later-formed connectors, for example. In other words, portions of the seed layer 114a exposed by the openings O7 may be referred to as conductive terminals, conductors, or conductive connectors, in the disclosure. In some embodiments, the patterning includes a laser drilling process, a mechanical drilling process, or other suitable processes. In alternative embodiments, the patterning includes an etching process such as a dry etching, a wet etching, or a combination thereof. The disclosure is not limited thereto.

[0082] Referring to FIG. 13, in some embodiments, a dicing (or singulation) process is sequentially performed to cut through the whole structure depicted in FIG. 12 (e.g., including a plurality of the package structure 100a interconnected therebetween) to form a plurality of individual and separated package structures 100a. For simplicity, only one package structure 100a is illustrated in FIG. 13 for illustrative purposes. In one embodiment, the dicing process is a wafer dicing process including mechanical blade sawing, or laser cutting; the disclosure is not limited thereto. Up to this, the package structure 100a is manufactured. The package structure 100a is referred to as an

integrated fan-out (InFO) package, which has dual-side terminals (e.g., **114a** and **174**).

[0083] In some embodiments, after dicing, a sidewall **SW110** of the redistribution circuit structure **110**, a sidewall **SW150** of the insulating encapsulation **150**, and a sidewall **SW160** of the redistribution circuit structure **160** are substantially aligned to each other, in the package structure **100a** depicted in FIG. **13**. That is, the sidewall **SW110** of the redistribution circuit structure **110**, the sidewall **SW150** of the insulating encapsulation **150**, and the sidewall **SW160** of the redistribution circuit structure **160** together constitute a sidewall **SW100a** of the package structure **100a**.

[0084] In one scenario of the disclosure, due to the dielectric layer **118a** is thinned, an overall thickness **H100a** of the package structure **100a** is reduced. In another scenario of the disclosure, due to the dielectric layer **118a** is thinned, a thickness **H141** (denoted in FIG. **8**) of the semiconductor substrate **141** of the semiconductor die **140** is increased to facilitate the heat dissipation of the package structure **100a**, where the overall thickness **H100a** of the package structure **100a** is maintained the same. In another scenario of the disclosure, due to the dielectric layer **118a** is thinned, the thickness **H130** of the connecting film **130** (as being the thermally conductive die attach film) is increased to facilitate the heat dissipation of the package structure **100a**, where the overall thickness **H100a** of the package structure **100a** is maintained the same.

[0085] In one scenario of the disclosure, due to the dielectric layer **118a** and the connecting film **130** (as being the non-thermally conductive die attach film) are thinned, an overall thickness **H100a** of the package structure **100a** is reduced. In another scenario of the disclosure, due to the dielectric layer **118a** and the connecting film **130** (as being the non-thermally conductive die attach film) are thinned, the thickness **H141** (denoted in FIG. **8**) of the semiconductor substrate **141** of the semiconductor die **140** is increased to facilitate the heat dissipation of the package structure **100a**, where the overall thickness **H100a** of the package structure **100a** is maintained the same.

[0086] In addition, additional conductive terminals may be mounted to the package structure **100a**, so to obtain another structure of InFO package of dual-side terminals. FIG. **14** is a schematic cross-sectional view of a package structure **100b** in accordance with some embodiments of the disclosure. The elements similar to or substantially the same as the elements described previously will use the same reference numbers, and certain details or descriptions (e.g., the materials, formation processes, positioning configurations, electrical connection, etc.) of the same elements would not be repeated herein. The package structure **100b** may be referred to as an InFO package, which has dual-side terminals.

[0087] Referring to FIG. **14**, in some embodiments, a plurality of under-ball metallurgy (UBM) patterns **182** and a plurality of conductive terminals **184** are sequentially formed on the dielectric layer **112a** of the redistribution circuit structure **110**, in accordance with step **S70** of FIG. **16**. In some embodiments, the UBM patterns **182** each are located between a respective one of the conductive terminals **184** and the dielectric layer **112a**. Due to the UBM patterns **182**, the adhesion strength between the conductive terminals **184** and the dielectric layer **112a** is enhanced. The formations and materials of the UBM patterns **182** and the conductive terminals **184** are similar to or substantially identical to the formations and materials of the UBM patterns **172** and the conductive terminals **174** as described in FIG. **10**, respectively; thus, are not repeated herein for brevity. In some embodiments, the UBM patterns **182** are disposed on (e.g., in physical contact with) the seed layer **114a** exposed by the openings **O7** formed in the dielectric layer **112a**. As shown in FIG. **14**, for example, the UBM patterns **182** are physically connected to and electrically connected to the seed layer **114a** of the redistribution circuit structure **110**.

[0088] In some embodiments, the conductive terminals **184** are electrically coupled to the redistribution circuit structure **110** through the UBM patterns **182**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the conductive pillars **120** through some of the UBM patterns **182** and the redistribution circuit structure **110**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the redistribution circuit structure **160** through some of the UBM patterns **182**, the redistribution circuit structure **110**, and the conductive

pillars **120**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the semiconductor die **140** through some of the UBM patterns **182**, the redistribution circuit structure **110**, the conductive pillars **120**, and the redistribution circuit structure **160**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the conductive terminals **174** through some of the UBM patterns **182**, the redistribution circuit structure **110**, the conductive pillars **120**, the redistribution circuit structure **160**, and some of the UBM patterns **172**. [0089] However, the disclosure is not limited thereto. In alternative embodiments, the UBM patterns **182** are be omitted, where the conductive terminals **184** are directly connected to (e.g., in physical contact with) the redistribution circuit structure **110** (e.g., the portions of the seed layer **114a** exposed by the openings O7). In such alternative embodiments, the conductive terminals **184** may be referred to as conductors or conductive connectors. In further alternative embodiments, the conductive terminals **184** are omitted, where the UBM patterns **182** are referred to as conductive terminals, conductors, or conductive connectors.

[0090] Up to here, the package structure **100b** is manufactured. The formation of the package structure **100b** may include, but not limited to, forming the UBM patterns **182** and the conductive terminals **184** on the redistribution circuit structure **110** prior to the dicing process as described in FIG. **13**.

[0091] In addition, one or more than one package (such as a memory package or the like) may be mounted to the package structure **100a** or **100b** having a structure of InFO package to form a semiconductor package having a package-on-package (PoP) structure. FIG. **15** is a schematic cross-sectional view of a package structure **1000** in accordance with some embodiments of the disclosure. The elements similar to or substantially the same as the elements described previously will use the same reference numbers, and certain details or descriptions (e.g., the materials, formation processes, positioning configurations, etc.) of the same elements would not be repeated herein. The package structure **1000** may be referred to as an InFO-PoP package.

[0092] Referring to FIG. **15**, in some embodiments, a package **800** is provided and bonded to the package structure **100b** depicted in FIG. **14** to form the package structure **1000** having the PoP structure, in accordance with step S80 of FIG. **16**. The details of the package structure **100b** have been previously described in FIG. **14** in conjunction with FIG. **1** through FIG. **13**, and thus are not repeated herein for brevity. In some embodiments, the package **800** includes a substrate **810**, semiconductor dies **820a** and **820b**, bonding wires **830a** and **830b**, conductive pads **840** and **850**, an insulating encapsulation **860**. Alternatively, the package **800** may further include the joining solder balls or pre-solders (not shown).

[0093] As shown in FIG. **15**, for example, the semiconductor die **820a** with a connecting film DA1 disposed thereon and the semiconductor die **820b** with a connecting film DA2 disposed thereon are provided and are disposed on the substrate **810**. In some embodiments, the connecting film DA1 is located between the semiconductor die **820a** and the substrate **810**, and the connecting film DA2 is located between the semiconductor die **820a** and the semiconductor die **820b**. In some embodiments, due to the connecting films DA1 and DA2 respectively provided between the semiconductor die **820a** and the substrate **810** and between the semiconductor dies **820a** and **820b**, the semiconductor dies **820a**, **820b** are stably adhered to the substrate **810**. In some embodiments, the connecting films DA1, DA2 may be, for example, a die attach film, a layer made of adhesives or epoxy resin, or the like.

[0094] For example, the semiconductor dies **820a** and **820b** are mounted on one surface (e.g., a surface S1) of the substrate **810**. The semiconductor dies **820a** and **820b** independently may be a logic chip (e.g., CPU, GPU, NPU, DPU, TPU, SoC, AP, a microcontroller, etc.), a memory chip (e.g., a DRAM chip, a RRAM chip, a MRAM chip, a SRAM chip, a NAND flash memory, WIO, a HBM module, a HMC module, etc.), a power management chip (e.g., a PMIC chip), a RF chip, a BB chip, a sensor chip, a MEMS chip, a signal processing chip (e.g., a DSP chip), a front-end chip (e.g., AFE chips), the like, or a combination thereof. In one embodiment, the semiconductor dies

820a and **820b** may be the same. For example, as shown in FIG. 16, the semiconductor dies **820a** and **820b** are DRAM chips, where the package **800** is referred to as a memory package. However, the disclosure is not limited thereto; alternatively, the semiconductor dies **820a** and **820b** may be different from each other.

[0095] In some embodiments, the bonding wires **830a** and **830b** are respectively used to provide electrical connections between the semiconductor dies **820a**, **820b** and some of the conductive pads **840** (such as bonding pads) located on the surface **S1** of the substrate **810**. Owing to the bonding wires **830a** and **830b**, the semiconductor dies **820a** and **820b** are electrically connected to the substrate **810**.

[0096] In some embodiments, the insulating encapsulation **860** is formed on the surface **S1** of the substrate **810** to encapsulate the semiconductor dies **820a**, **820b**, the bonding wires **830a**, **830b** and the conductive pads **840** to protect these components. A formation and material of the insulating encapsulation **860** is similar to or substantially identical to the process and material of forming the encapsulation material **150m** as described in FIG. 7 and/or the insulating encapsulation **150** as described in FIG. 8, and thus are not repeated herein for brevity. In one embodiment, the insulating encapsulation **860** is the same as the insulating encapsulation **150**. In an alternative embodiment, the insulating encapsulation **860** is different from the insulating encapsulation **150**, the disclosure is not limited thereto.

[0097] In some embodiments, interconnects (not shown) and/or through-insulator-vias (not shown) embedded in the substrate **810** may be used to provide electrical connection between the conductive pads **840** and the conductive pads **850** (such as bonding pads) that are located on another surface (e.g., a surface **S2** opposite to the surface **S1** in the direction **Z**) of the substrate **810**. In some embodiments, some of the conductive pads **850** are electrically coupled to the semiconductor dies **820a** and **820b** through these through-insulator-vias and/or interconnects in addition to some of the conductive pads **840** and the bonding wires **830a**, **830b**. Furthermore, some of the conductive pads **840** may be electrically coupled to each other through the interconnects, and some of the conductive pads **850** may be electrically coupled to each other through the interconnects.

[0098] In some embodiments, the conductive pads **850** of the package **800** are connected to and electrically coupled to the conductive terminals **184** of the package structure **100b**, and thus the package **800** is electrically coupled to the package structure **100b**. In some embodiments, the redistribution circuit structure **110** is electrically coupled to the substrate **810** of the package **800** through the conductive terminals **184** and the conductive pads **850**. In some embodiments, the semiconductor dies **820a**, **820b** are electrically communicated to the semiconductor die **140**.

[0099] In addition, as shown in FIG. 15, an insulating material **190** is optionally disposed in a gap between the package structure **100b** and the package **800** and wraps around the conductive terminals **184** of the package structure **100b**, for example. Owing to the insulating material **190**, the bonding strength between the package structure **100b** and the package **800** is enhanced, thereby improving the reliability of the package structure **1000**. The insulating material **190** may be an underfill made of any acceptable material, such as polymer, epoxy, molding underfill, or the like. The insulating material **190** may be formed by underfill dispensing or any other suitable method. Alternatively, the insulating material **190** may be omitted.

[0100] The formation of the package structure **1000** may include, but not limited to, bonding the package **800** to the package structure **100b** after forming the conductive terminals **184** as described in FIG. 14 and prior to the dicing process as described in FIG. 13; applying the insulating material **190** in the gap between the package structure **100b** and the package **800**; and performing the dicing process as described in FIG. 13 to cut through a plurality of the packages **800** interconnected therebetween, a plurality of the package structures **100b** interconnected therebetween, and the insulating material **190** interposed therebetween into a plurality of individual and separated package structures **1000**. For simplicity, only one package structure **1000** is illustrated in FIG. 15

for illustrative purposes. In some embodiments, after dicing, a sidewall SW**800** of the package **800**, a sidewall SW**190** of the insulating material **190**, and the sidewall SW**100b** of the package structure **100b** are substantially aligned to each other, in the package structure **1000** depicted in FIG. **15**. That is, the sidewall SW**800** of the package **800**, the sidewall SW**190** of the insulating material **190**, and the sidewall SW**100b** of the package structure **100b** together constitute a sidewall of the package structure **1000**. In the case, for the package structure **1000** of FIG. **15**, a lateral size W**800** of the package **800** is substantially equal to a lateral size W**100b** of the package structure **100b**.

[0101] However, the disclosure is not limited thereto; alternatively, the formation of the package structure **1000** may include bonding the package **800** to the package structure **100b** after forming the conductive terminals **184** as described in FIG. **14** and prior to the dicing process as described in FIG. **13**; applying the insulating material **190** in the gap between the package structure **100b** and the package **800**; and performing the dicing process as described in FIG. **13** to cut through only the insulating material **190** and a plurality of the package structures **100b** interconnected therebetween into individual and separated package structures **1000**. In the case, the lateral size of the package **800** is less than the lateral size of the package structure **100b**, where the sidewall of the package **800** is not aligned with the sidewall of the insulating material **190** and the sidewall of the package structure **100b**. The sidewall of the package **800** may be free of the insulating material **190**. The sidewall of the package **800** may be at least partially covered by the insulating material **190**.

[0102] Or alternatively, the formation of the package structure **1000** may include bonding the package **800** to the package structure **100b** after the dicing process as described in FIG. **13**; and then applying the insulating material **190** in the gap between the package structure **100b** and the package **800** to form the package structure **1000**. In the case, the lateral size of the package **800** is may be less than, greater than, or substantially equal to the lateral size of the package structure **100b**, where the sidewall of the package **800** is not aligned with the sidewall of the insulating material **190** and the sidewall of the package structure **100b**. The sidewall of the package **800** may be free of the insulating material **190**. The sidewall of the package **800** may be at least partially covered by the insulating material **190**.

[0103] In the disclosure, alternatively, the redistribution circuit structure **110** may be substituted by a redistribution circuit structure **110A**. In some embodiments, the redistribution circuit structure **110A** includes at least one dielectric layer **112** (e.g., **112a** and **112b**), at least one seed layer **114** (e.g., **114a** and **114b**), at least one conductive layer **116** (e.g., **116a** and **116b**), a dielectric layer **118b**, and a dielectric **50**. However, the numbers of layers of the dielectric layer **112**, the seed layer **114**, and the conductive layer **116** are not limited to what is depicted in the disclosure, where the numbers of the layers of the dielectric layer **112**, the seed layer **114**, and the conductive layer **116** may be one or more than one depending upon the demand and design requirements. In some embodiments, one conductive layer **116** includes a line portion extending along a horizontal direction (e.g., a direction X or Y), a via portion extending along a vertical direction (e.g., a direction Z) connecting to the line portion, or a combination thereof. The directions X, Y and Z may be different from each other. For example, the directions X, Y and Z are perpendicular to each other. FIG. **18** is a flow chart illustrating a method of manufacturing the redistribution circuit structure **110A** in accordance with some embodiments of the disclosure. FIG. **19** through FIG. **22** are schematic cross-sectional views of various stages in a manufacturing method of a package structure **200a** in accordance with some embodiments of the disclosure. The elements similar to or substantially the same as the elements described previously will use the same reference numbers, and certain details or descriptions (e.g., the materials, formation processes, positioning configurations, etc.) of the same elements would not be repeated herein.

[0104] Referring to FIG. **19**, in some embodiments, a planarizing process is performed on the dielectric layer **118m** to form a dielectric layer **118b** exposing the conductive layer **116b**, following the process as described in FIG. **3**; in accordance with step S**12b** of FIG. **18**. It is appreciated that the processes as described in FIG. **1** through FIG. **3** are also in accordance with step S**11b** of FIG.

18. In some embodiments, during the planarizing process, the dielectric layer **118m** is thinned until the surface **TS116b** of the conductive layer **116b** is accessibly revealed. For example, the dielectric layer **118b** is disposed on (e.g., in physical contact with) the dielectric layer **112b** exposed by the conductive layer **116b** and the seed layer **114b** and laterally covers (e.g., in physical contact with) the conductive layer **116b** and the seed layer **114b**. In some embodiments, a surface **TS118b** of the dielectric layer **118b** is considered as a substantially planar surface, which has a surface roughness **R2** (e.g., a difference between a surface peak to a surface valley along the direction **Z**) being less than or substantially equal to 2 μm . In one embodiment, the surface roughness **R2** is ranging about 0.5 μm to about 2 μm . In an alternative embodiment, the surface roughness **R2** is ranging about 1 μm to about 2 μm . In the disclosure, the surface roughness **R2** is in an acceptable tolerance, for example, less than or substantially equal to 2 μm . As the surface roughness **R2** falls within the acceptable tolerance, the surface **TS118b** of the dielectric layer **118b** is substantially flat and planar. As shown in FIG. 19, the surface **TS118b** of the dielectric layer **118b**, for example, provides a high degree of coplanarity and flatness. Due to the high degree of coplanarity and flatness in the surface **TS118b** of the dielectric layer **118b**, the formation of the later-formed layer(s) and/or element(s) is beneficial, such as a process window of a pick-and-place process for a semiconductor die is enlarged.

[0105] In some embodiments, the dielectric material layer **118m** is planarized by a mechanical grinding process, a CMP process, an etching process, or combinations thereof. The etching process may include a dry etching, a wet etching, or a combination thereof. After the planarizing process, a cleaning process may be optionally performed, for example to clean and remove the residue generated from the planarizing process. However, the disclosure is not limited thereto, and the planarizing process may be performed through any other suitable method. In some embodiments, during the planarizing process of the dielectric material layer **118m**, portions of the conductive layer **116b** are slightly planarized as well. As shown in FIG. 19, the surface **TS118b** of the dielectric layer **118b** is substantially leveled with the surface **TS116b** of the conductive layer **116b**, for example. For example, the surface **TS118b** of the dielectric layer **118b** and the surface **TS116b** of the conductive layer **116b** are substantially coplanar to each other. As shown in FIG. 19, for example, the dielectric layer **118b** has a thickness **H118b** ranging from about 2 μm to about 30 μm .

[0106] Referring to FIG. 20, in some embodiments, a dielectric layer **50** is formed on the structure depicted on FIG. 19. For example, the dielectric layer **50** is disposed on (e.g., in physical contact with) the metallization layer **ML2** and the dielectric layer **118b** laterally covering the metallization layer **ML2**. In some embodiments, the dielectric layer **50** has a plurality of openings **O8** each exposing a portion of the conductive layer **116b** and at least one trench (referred to as hole, opening, recess) **TH** exposing a portion of the conductive layer **116b** and a portion of the dielectric layer **118b**. As shown in FIG. 20, through the openings **O7**, the surface **TS116b** of the conductive layer **116b** is partially exposed for electrically connecting to later-formed connectors, for example. On the other hand, the trenches **TH** is corresponding to a positioning location of a semiconductor die later-disposed thereon. In some embodiments, the dielectric layer **50** is formed by, but not limited to, forming a blanket layer of dielectric material over the surface **TS116b** of the conductive layer **116b** and the surface **TS118b** of the dielectric layer **118b** (in accordance with step **S13b** of FIG. 18), and patterning the dielectric material blanket layer to form the dielectric layer **50** with the openings **O8** exposing portions of the conductive layer **116b** underneath thereto and the trench **TH** exposing portions of the conductive layer **116b** and the dielectric layer **118b** underneath thereto (in accordance with step **S14b** of FIG. 18). The patterning may include a dry etching, a wet etching, or a combination thereof. The formation and material of the dielectric layer **50** may be the same or similar to the process and material of forming the dielectric layer **112a**, **112b**, and/or **118b** as described in FIG. 1 through FIG. 3, and thus are not repeated therein for brevity. In one embodiment, the material of the dielectric layer **50** is the same as the material of the dielectric layer **112a**, **112b**, and/or **118b**. For example, the dielectric material layers **118b** and **50** are made of PI,

while at least one of the dielectric layers **112a** and **112b** is also made of PI. In an alternative embodiment, the material of the dielectric layer **50** is different from the material of the dielectric layer **112a**, **112b**, and/or **118b**; the disclosure is not limited thereto. The dielectric layer **118b** and dielectric layer **50** may be together referred to as a capping layer of the redistribution circuit structure **110A**.

[0107] In some embodiments, the dielectric layers **112a**, **112b**, **118b**, and **50** are together referred to as a dielectric structure of the redistribution circuit structure **110A**, a metallization layer **ML1** (including **114a** and **116a**; referred to as a redistribution layer/line) and a metallization layer **ML2** (including **114b** and **116b**; referred to as a redistribution layer/line) are together referred to as a routing structure of the redistribution circuit structure **110A**. If considering the dielectric layers **112a**, **112b**, **118b**, and **50** are made of the same material, there is no clear interface between any two adjacent layers of the dielectric layers **112a**, **112b**, **118b**, and **50**. On the other hand, if considering any two adjacent layers of the dielectric layers **112a**, **112b**, **118b**, and **50** are made of different materials, there is a clear interface between the two adjacent layers of the dielectric layers **112a**, **112b**, **118b**, and **50**.

[0108] Up to here, the redistribution circuit structure **110A** is manufactured. For example, in the redistribution circuit structure **110A**, a first build-up layer including the metallization layer **ML1** and the dielectric layer **112a** is electrically connected to a second build-up layer including the metallization layer **ML2** and the dielectric layer **112b**. Although only one first build-up layer and one second build-up layer are included in the redistribution circuit structure **110A** as shown in FIG. **20** for illustrative purposes, the number of each of the first and second build-up layers may not be limited to what is depicted in FIG. **20**. For example, the number of each of the first and second build-up layers may be one or more than one. The disclosure is not limited thereto.

[0109] Referring to FIG. **21**, in some embodiments, at least one conductive pillar **120** and at least one semiconductor die **140** are formed on the redistribution circuit structure **110A** and over the carrier substrate **102**. For illustrative purposes, the at least one conductive pillar **120** includes a plurality of conductive pillars **120** (e.g., four conductive pillars **120**), and at least one semiconductor die **140** includes one semiconductor die **140**, as presented in FIG. **21**. However, the number of the conductive pillars **120** and the number of the semiconductor die **140** are not limited to what is depicted in the disclosure, and may be selected and designated based on the demand and design requirements. The number of the conductive pillars **120** may be more than or less than four, and the number of the semiconductor die **140** may be more than one. For example, the number of the conductive pillars **120** can be adjusted by changing the number of the openings **O8** formed in the dielectric layer **50**, and the number of the semiconductor die **140** can be adjusted by changing the number of the trench **TH** formed in the dielectric layer **50**. In some embodiments, the conductive pillars **120** and the semiconductor die **140** are arranged side-by-side on a side of the redistribution circuit structure **110A**.

[0110] In some embodiments, the conductive pillars **120** are disposed on the redistribution circuit structure **110A** and extend into the openings **O8** to physically connect to and electrically connect to the metallization layer **ML2** of the redistribution circuit structure **110A**. As shown in FIG. **21**, the conductive pillars **120** are in physical contact with the conductive layer **116b** through the openings **O8** formed in the dielectric layer **50**, for example. In some embodiments, the conductive pillars **120** each include a seed pattern **122** and a conductive via **124** standing thereon. As shown in FIG. **21**, the seed patterns **122** may be disposed on the surface **TS50** of the dielectric layer **50** and further extended into the openings **O8**, and the conductive vias **124** may be respectively disposed on (e.g., in physical contact with) the seed patterns **122**. In the case, the seed patterns **122** penetrate through the dielectric layer **50**, and sidewalls of the openings **O8** are completely covered by (e.g., lined with) the seed patterns **122**. In other words, the conductive pillars **120** penetrate through the dielectric layer **50** and stand on the surface **TS118b** of the dielectric layer **118b** and the surface **TS116b** of the conductive layer **116b**, where the conductive vias **124** are electrically coupled to the

conductive layer **116b** through the seed patterns **122**. In some embodiments, in the vertical projection on the dielectric layer **112a** along the direction Z, the conductive vias **124** are completely overlapped with the seed patterns **122**. That is to say, a sidewall of one conductive via **124** may be substantially aligned with a sidewall of a respective one seed pattern **122**. For example, one conductive via **124** and the respective one seed pattern **122** share the same geometrical shape on the top view, e.g., the X-Y plane. The details of the conductive pillars **120** including the seed patterns **122** and the conductive vias **124** have been previously described in FIG. 6, and thus are not repeated herein for brevity. In some embodiments, the conductive pillars **120** may be InFO vias, vertical connectors, or vertical connections. In some embodiments, the conductive pillars **120** are arranged along but not on a cutting line (not shown) between two package structures (e.g., two of the package structures **200a**).

[0111] Continued on FIG. 21, in some embodiments, the semiconductor die **140** is disposed on the redistribution circuit structure **110A** and next to the conductive pillars **120**. In some embodiments, the semiconductor die **140** is picked and placed over the redistribution circuit structure **110A** and disposed in the trench TH formed in the dielectric layer **50** onto the surface TS**118b** of the dielectric layer **118b** and the surface TS**116b** of the conductive layer **116b**, where the semiconductor die **140** is laterally distant from the conductive pillars **120**. In some embodiments, the semiconductor die **140** includes a semiconductor substrate **141** having an active surface **141t** and a backside surface **141b** opposite to the active surface **141t**, a plurality of pads **142** distributed on the active surface **141t**, a passivation layer **143** covering the active surface **141t** and a portion of the pads **142**, a post passivation layer **144** covering the passivation layer **143** and a portion of the pads **142**, a plurality of conductive vias **145** connecting to the pads **142** exposing by the passivation layer **143** and the post passivation layer **144**, and a protection layer **146** disposed on and covering the post passivation layer **144** and the conductive vias **145**. The details of the semiconductor die **140** including the semiconductor substrate **141**, the pads **142**, the passivation layer **143**, the post passivation layer **144**, the conductive vias **145**, and the protection layer **146** have been previously described in FIG. 6, and thus are not repeated herein for brevity. However, the disclosure may not be limited thereto. Alternatively, the illustrated top surfaces of the conductive vias **145** may be accessibly exposed by the protection layer **146**. Or alternatively, the post passivation layer **144** and/or the protection layer **146** may be omitted. Or alternatively, the conductive vias **145** and the protection layer **146** are omitted, where the post passivation layer **144** may or may not be omitted. [0112] In certain embodiments, additional semiconductor die(s) of the same type or different types may be included. The additional semiconductor die(s) may include digital chips, analog chips, or mixed signal chips, such as ASIC chips, sensor chips, wireless and RF chips, memory chips, logic chips, voltage regulator chips, or the like. The disclosure is not limited thereto. It should be appreciated that the illustration of the semiconductor die **140** and its components throughout all figures is schematic and is not in scale.

[0113] As illustrated in FIG. 21, in some embodiments, the semiconductor die **140** is bonded to the redistribution circuit structure **110A** by adhering onto the redistribution circuit structure **110A** with a connecting film **130**. The semiconductor die **140** (e.g., the backside surface **141b** thereof) may be adhered to the surface TS**118b** of the dielectric layer **118b** and the surface TS**116b** of the conductive layer **116b** of the redistribution circuit structure **110A** by the connecting film **130**. For example, as shown in FIG. 21, the connecting film **130** is sandwiched between the semiconductor die **140** and the redistribution circuit structure **110A**. Owing to the connecting film **130**, the semiconductor die **140** is stably adhered to the dielectric layer **118b** and the conductive layer **116b** of the redistribution circuit structure **110A**. Owing to the coplanarity of the dielectric layer **118b** (having the surface TS**118b** with high degree of coplanarity and flatness) and the conductive layer **116b**, there is no or little air or void trapped between the connecting film **130** and the redistribution circuit structure **110A**, thereby an undesired movement of the semiconductor die **140** and/or an insulating encapsulation **150** (see FIG. 22) surrounding the semiconductor die **140** and/or the

moisture trapped by the void and/or the risk of “pop-corn” may be suppressed, which enhancing the reliability and performance of the package structure **200a**.

[0114] The details of the connecting film **130** have been previously described in FIG. **6**, and thus are not repeated herein for brevity. In some embodiments, a thickness **H130** of the connecting film **130** is ranging from about 5 μm to about 200 μm . In the embodiments of which the connecting film **130** is the thermally conductive die attach film, the connecting film **130** thermally couples the semiconductor die **140** and the redistribution circuit structure **110A**, which helps to dissipate heat from the semiconductor die **140**; thus, the thickness **H130** of the connecting film **130** can be thick to ensure a high surface coverage capability. In the embodiments of which the connecting film **130** is the non-thermally conductive die attach film, in order to allow the connecting film **130** being capable of thermally coupling the semiconductor die **140** and the redistribution circuit structure **110A** for the heat dissipation of the semiconductor die **140**, the thickness **H130** of the connecting film **130** can be thin. In other words, the heat dissipation of the package structure **200a** may be controlled (e.g., to be improved or maintained based on the demand and design requirements) by adjusting the thermal conductivity and/or the thickness **H130** of the connecting film **130**, for example, in the disclosure. In some embodiments, the connecting film **130** is disposed between the semiconductor die **140** and the conductive layer **116b** (exposed by the dielectric layers **50** and **118b**) of the redistribution circuit structure **110A**. The conductive layer **116b** exposed by the trench **TH** formed in the dielectric layer **50** and disposed underneath the semiconductor die **140** is thermally coupled to the semiconductor die **140**, as shown in FIG. **21**, for example. Owing to such configuration (e.g., the connecting film **130** directly contacting to the conductive layer **116b**), a heat dissipation of the heat generated from the semiconductor die **140** is further enhanced.

[0115] In FIG. **21**, for example, the semiconductor die **140** and the conductive pillars **120** are arranged next to each other along the X-Y plane. In some embodiments, the semiconductor die **140** are not overlapped with the conductive pillars **120** in the direction Z, but are overlapped with each other in the direction X and/or the direction Y. In one embodiment, a height of the conductive pillars **120** is greater than a height of the semiconductor die **140**, as shown in FIG. **21**.

Alternatively, the height of the conductive pillars **120** may be less than or substantially equal to the height of the semiconductor die **140**. In some embodiments, the surface **TS130** of the connecting film **130** is substantially leveled with the surface **TS50** of the dielectric layer **50** in the direction Z, as shown in FIG. **21**. However, the disclosure is not limited thereto; alternatively, the surface **TS130** of the connecting film **130** may be lower than or higher than the surface **TS50** of the dielectric layer **50** in the direction Z.

[0116] Referring to FIG. **22**, in some embodiments, the processes as described in FIG. **7** through FIG. **13** are performed on the structure depicted in FIG. **21** to form the package structure **200a**. For example, an insulating encapsulation **150** is disposed on (e.g., in physical contact with) the semiconductor die **140**, the conductive pillars **120**, and the redistribution circuit structure **110A** exposed by the semiconductor die **140** and the conductive pillars **120**. As illustrated in FIG. **22**, the conductive pillars **120** and the semiconductor die **140** may be laterally encapsulated in the insulating encapsulation **150**. In the case, a surface of the insulating encapsulation **150**, surfaces of the conductive vias **145** of the semiconductor die **140**, and surfaces of the conductive pillars **120** are substantially leveled with and substantially coplanar to each other. As show in FIG. **22**, a thickness **H150** of the insulating encapsulation **150** is less than a sum of the thickness **H130** of the connecting film **130** and a thickness **H140** of the semiconductor die **140**, for example. In some embodiments, a redistribution circuit structure **160** is disposed on the conductive pillars **120**, the semiconductor die **140** and the insulating encapsulation **150**, and is electrically connected to the conductive pillars **120** and the semiconductor die **140**. For example, at least some of the conductive pillars **120** are electrically coupled to the semiconductor die **140** through the redistribution circuit structure **160**, and the redistribution circuit structure **110A** is electrically coupled to the semiconductor die **140** through the redistribution circuit structure **160** and at least some of the

conductive pillars **120**.

[0117] A plurality of UBM patterns **172** are physically connected to and electrically connected to the redistribution circuit structure **160**, for example. In the case, a plurality of conductive terminals **174** are physically connected and electrically connected to the UBM patterns **172**, and are electrically coupled to the redistribution circuit structure **160** through the UBM patterns **172**. In some embodiments, at least some of the conductive terminals **174** are electrically coupled to the semiconductor die **140** through the redistribution circuit structure **160** and respective ones of the UBM patterns **172**. In some embodiments at least some of the conductive terminals **174** are electrically coupled to the redistribution circuit structure **110A** through respective ones of the UBM patterns **172**, the redistribution circuit structure **160**, and at least some of the conductive pillars **120**. However, the disclosure is not limited thereto. In some alternative embodiments, the UBM patterns **172** may be omitted. In such alternative embodiments, the conductive terminals **174** may be directly connected to (e.g., in physical contact with) the redistribution circuit structure **160** (e.g., the portions of the conductive layer **166c** exposed by openings **O6** formed in the dielectric layer **168**). The conductive terminals **174** may be referred to as conductors or conductive connectors, in the disclosure.

[0118] As shown in FIG. 22, for example, the dielectric layer **112a** includes a plurality of openings **O7** each exposing a portion of the seed layer **114a**. As shown in FIG. 22, through the openings **O7**, a surface **BS114a** of the seed layer **114a** is partially exposed for electrically connecting to later-formed connectors, for example. In other words, portions of the seed layer **114a** exposed by the openings **O7** may be referred to as conductive terminals, conductors, or conductive connectors, in the disclosure. In some embodiments, the package structure **200a** is referred to as an InFO package, which has dual-side terminals (e.g., **114a** and **174**). In the disclosure, the redistribution circuit structure **160** may be referred to as a front-side redistribution circuit structure or layer of the semiconductor die **140**, while the redistribution circuit structure **110A** may be referred to as a back-side redistribution circuit structure or layer of the semiconductor die **140**.

[0119] The details, formations, and materials of the insulating encapsulation **150**, the redistribution circuit structure **160** (including a first building layer (having a dielectric layer **162a** and a metallization layer **ML3** (including a seed layer **164a** and a conductive layer **166a**)), a second building layer (having a dielectric layer **162b** and a metallization layer **ML4** (including a seed layer **164b** and a conductive layer **166b**)), a third building layer (having a dielectric layer **162c** and a metallization layer **ML5** (including a seed layer **164c** and a conductive layer **166c**)), and a dielectric layer **168**), the UBM patterns **172**, and the conductive terminals **174** have been previously described in FIG. 7 through FIG. 13, respectively; thus, are not repeated herein for brevity. In some embodiments, a sidewall **SW110A** of the redistribution circuit structure **110A**, a sidewall **SW150** of the insulating encapsulation **150**, and a sidewall **SW160** of the redistribution circuit structure **160** are substantially aligned to each other, in the package structure **200a** depicted in FIG. 22. That is, the sidewall **SW110A** of the redistribution circuit structure **110A**, the sidewall **SW150** of the insulating encapsulation **150**, and the sidewall **SW160** of the redistribution circuit structure **160** together constitute a sidewall **SW200a** of the package structure **200a**.

[0120] In one scenario of the disclosure, due to the dielectric layer **118b** is thinned and the trench **TH** formed in the dielectric layer **50**, an overall thickness **H200a** of the package structure **200a** is reduced. In another scenario of the disclosure, due to the dielectric layer **118b** is thinned and the trench **TH** formed in the dielectric layer **50**, a thickness **H141** of the semiconductor substrate **141** of the semiconductor die **140** is increased to facilitate the heat dissipation of the package structure **200a**, where the overall thickness **H200a** of the package structure **200a** is maintained the same. In another scenario of the disclosure, due to the dielectric layer **118b** is thinned and the trench **TH** formed in the dielectric layer **50**, the thickness **H130** of the connecting film **130** (as being the thermally conductive die attach film) is increased to facilitate the heat dissipation of the package structure **200a**, where the overall thickness **H200a** of the package structure **200a** is maintained the

same.

[0121] In one scenario of the disclosure, due to the dielectric layer **118b** and the connecting film **130** (as being the non-thermally conductive die attach film) are thinned and the trench TH formed in the dielectric layer **50**, an overall thickness **H200a** of the package structure **200a** is reduced. In another scenario of the disclosure, due to the dielectric layer **118b** and the connecting film **130** (as being the non-thermally conductive die attach film) are thinned and the trench TH formed in the dielectric layer **50**, the thickness **H141** of the semiconductor substrate **141** of the semiconductor die **140** is increased to facilitate the heat dissipation of the package structure **200a**, where the overall thickness **H200a** of the package structure **200a** is maintained the same.

[0122] In addition, additional conductive terminals (e.g., UBM patterns **182** and/or conductive terminals **184**) may be mounted to the package structure **200a**, so to obtain another structure of InFO package having dual-side terminals. FIG. **23** is a schematic cross-sectional view of a package structure **200b** in accordance with some embodiments of the disclosure. The elements similar to or substantially the same as the elements described previously will use the same reference numbers, and certain details or descriptions (e.g., the materials, formation processes, positioning configurations, electrical connection, etc.) of the same elements would not be repeated herein. In some embodiments, the UBM patterns **182** and the conductive terminals **184** are sequentially formed on the dielectric layer **112a** of the redistribution circuit structure **110A**. In some embodiments, the UBM patterns **182** each are located between a respective one of the conductive terminals **184** and the dielectric layer **112a**. Due to the UBM patterns **182**, the adhesion strength between the conductive terminals **184** and the dielectric layer **112a** is enhanced. The formations and materials of the UBM patterns **182** and the conductive terminals **184** are similar to or substantially identical to the formations and materials of the UBM patterns **172** and the conductive terminals **174** as described in FIG. **10**, respectively; thus, are not repeated herein for brevity.

[0123] Referring to FIG. **23**, in some embodiments, the UBM patterns **182** are disposed on (e.g., in physical contact with) the seed layer **114a** exposed by the openings O7 formed in the dielectric layer **112a**. As shown in FIG. **23**, for example, the UBM patterns **182** are physically connected to and electrically connected to the seed layer **114a** of the redistribution circuit structure **110A**. In some embodiments, the conductive terminals **184** are electrically coupled to the redistribution circuit structure **110A** through the UBM patterns **182**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the conductive pillars **120** through some of the UBM patterns **182** and the redistribution circuit structure **110A**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the redistribution circuit structure **160** through some of the UBM patterns **182**, the redistribution circuit structure **110A**, and the conductive pillars **120**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the semiconductor die **140** through some of the UBM patterns **182**, the redistribution circuit structure **110A**, the conductive pillars **120**, and the redistribution circuit structure **160**. In some embodiments, some of the conductive terminals **184** are electrically coupled to the conductive terminals **174** through some of the UBM patterns **182**, the redistribution circuit structure **110A**, the conductive pillars **120**, the redistribution circuit structure **160**, and some of the UBM patterns **172**. [0124] However, the disclosure is not limited thereto. In alternative embodiments, the UBM patterns **182** are omitted, where the conductive terminals **184** are directly connected to (e.g., in physical contact with) the redistribution circuit structure **110A** (e.g., the portions of the seed layer **114a** exposed by the openings O7). In such alternative embodiments, the conductive terminals **184** may be referred to as conductors or conductive connectors. In further alternative embodiments, the conductive terminals **184** are omitted, where the UBM patterns **182** are referred to as conductive terminals, conductors, or conductive connectors.

[0125] The package structure **200b** may be referred to as an InFO package, which has dual-side terminals. The formation of the package structure **200b** may include, but not limited to, forming the UBM patterns **182** and the conductive terminals **184** on the redistribution circuit structure **110A**

after forming the openings O7 in the dielectric layer **112a** as described in FIG. 12 and prior to the dicing process as described in FIG. 13.

[0126] In addition, one or more than one package (such as a memory package or the like) may be mounted to the package structure **200a** or **200b** having a structure of InFO package to form a semiconductor package having a PoP structure. FIG. 24 is a schematic cross-sectional view of a package structure **2000** in accordance with some embodiments of the disclosure. The elements similar to or substantially the same as the elements described previously will use the same reference numbers, and certain details or descriptions (e.g., the materials, formation processes, positioning configurations, etc.) of the same elements would not be repeated herein. Referring to FIG. 24, in some embodiments, a package **800** is provided and bonded to the package structure **200b** depicted in FIG. 23 to form the package structure **2000** having the PoP structure. In addition, as shown in FIG. 25, an insulating material **190** is optionally disposed in a gap between the package structure **200b** and the package **800** and wraps around the conductive terminals **184** of the package structure **200b**, for example. Owing to the insulating material **190**, the bonding strength between the package structure **200b** and the package **800** is enhanced, thereby improving the reliability of the package structure **2000**. Alternatively, the insulating material **190** may be omitted. The details of the package **800** and its bonding method and the details of the insulating material **190** have been previously described in FIG. 15, and thus are not repeated herein for brevity. The package structure **2000** may be referred to as an InFO-PoP package.

[0127] The formation of the package structure **2000** may include, but not limited to, bonding the package **800** to the package structure **200b** after forming the conductive terminals **184** as described in FIG. 14 and prior to the dicing process as described in FIG. 13; applying the insulating material **190** in the gap between the package structure **200b** and the package **800**; and performing the dicing process as described in FIG. 13 to cut through a plurality of the packages **800** interconnected therebetween, a plurality of the package structures **200b** interconnected therebetween, and the insulating material **190** interposed therebetween into a plurality of individual and separated package structures **2000**. For simplicity, only one package structure **2000** is illustrated in FIG. 24 for illustrative purposes. In some embodiments, after dicing, a sidewall SW**800** of the package **800**, a sidewall SW **190** of the insulating material **190**, and the sidewall SW**200b** of the package structure **200b** are substantially aligned to each other, in the package structure **2000** depicted in FIG. 25. That is, the sidewall SW**800** of the package **800**, the sidewall SW**190** of the insulating material **190**, and the sidewall SW**200b** of the package structure **200b** together constitute a sidewall of the package structure **2000**. In the case, for the package structure **2000** of FIG. 25, a lateral size W**800** of the package **800** is substantially equal to a lateral size W**200b** of the package structure **200b**.

[0128] However, the disclosure is not limited thereto; alternatively, the formation of the package structure **2000** may include bonding the package **800** to the package structure **200b** after forming the conductive terminals **184** as described in FIG. 14 and prior to the dicing process as described in FIG. 13; applying the insulating material **190** in the gap between the package structure **200b** and the package **800**; and performing the dicing process as described in FIG. 13 to cut through only the insulating material **190** and a plurality of the package structures **200b** interconnected therebetween into individual and separated package structures **2000**. In the case, the lateral size of the package **800** is less than the lateral size of the package structure **200b**, where the sidewall of the package **800** is not aligned with the sidewall of the insulating material **190** and the sidewall of the package structure **200b**. The sidewall of the package **800** may be free of the insulating material **190**. The sidewall of the package **800** may be at least partially covered by the insulating material **190**.

[0129] Or alternatively, the formation of the package structure **2000** may include bonding the package **800** to the package structure **200b** after the dicing process as described in FIG. 13; and then applying the insulating material **190** in the gap between the package structure **200b** and the package **800** to form the package structure **2000**. In the case, the lateral size of the package **800** is

may be less than, greater than, or substantially equal to the lateral size of the package structure **200b**, where the sidewall of the package **800** is not aligned with the sidewall of the insulating material **190** and the sidewall of the package structure **200b**. The sidewall of the package **800** may be free of the insulating material **190**. The sidewall of the package **800** may be at least partially covered by the insulating material **190**.

[0130] In some embodiments, the package structures **100a**, **100b**, **1000**, **200a**, **200b**, and/or **2000** may be mounted to an additional semiconductor component to form an assembly by a wafer level packaging (WLP), a chip-on-wafer-on-substrate (CoWoS) process, a chip-on-chip-on-substrate (CoCoS) process, etc. The additional semiconductor component may include an interposer, a package substrate, a printed circuit board (PCB), a printed wiring board, and/or other carrier that is capable of carrying integrated circuits. The disclosure is not limited thereto. The assembly may be a part of an electronic system for such as computers (e.g., high-performance computer), computational devices used in conjunction with an artificial intelligence system, wireless communication devices, computer-related peripherals, entertainment devices, etc. The assembly including the semiconductor structure(s) discussed herein may provide high bandwidth data communication. It should be noted that other electronic applications are also possible.

Alternatively, additional terminals may be physical and electrical contact with the additional semiconductor component opposite to the package structures **100a**, **100b**, **1000**, **200a**, **200b**, and/or **2000** for electrical connection to any other external component(s).

[0131] In accordance with some embodiments, a package structure includes a package structure includes a first redistribution circuit structure, a semiconductor die, a connecting film, and a second redistribution circuit structure. The first redistribution circuit structure includes a dielectric structure and a routing structure disposed therein, where the dielectric structure includes a trench exposing the routing structure. The semiconductor die is disposed on and electrically coupled to the first redistribution circuit structure. The connecting film is disposed in the trench and between the semiconductor die and the first redistribution circuit structure, and the semiconductor die is thermally coupled to the routing structure through the connecting film. The second redistribution circuit structure is disposed on and electrically coupled to the semiconductor die, the second redistribution circuit structure is electrically coupled to the first redistribution circuit structure, and the semiconductor die is disposed between the first redistribution circuit structure and the second redistribution circuit structure.

[0132] In accordance with some embodiments, a package structure includes a package structure includes a first redistribution circuit structure, a semiconductor die, a connecting film, and a second redistribution circuit structure. The first redistribution circuit structure includes a metallization layer and a capping layer disposed over the metallization layer, where a first surface of the capping layer has a surface roughness being less than or substantially equal to 2 μm . The semiconductor die is disposed on the first surface of the capping layer and electrically coupled to the first redistribution circuit structure. The connecting film is disposed between the semiconductor die and the capping layer of the first redistribution circuit structure, and the semiconductor die is thermally coupled to the metallization layer through the connecting film. The second redistribution circuit structure is disposed on and electrically coupled to the semiconductor die, the second redistribution circuit structure is electrically coupled to the first redistribution circuit structure, and the semiconductor die is disposed between the first redistribution circuit structure and the second redistribution circuit structure.

[0133] In accordance with some embodiments, a method of manufacturing a package structure includes the following steps: forming a first redistribution circuit structure includes: forming a metallization layer; disposing a dielectric material over the metallization layer; and planarizing the dielectric material to form a capping layer over the metallization layer, a first surface of the capping layer having a surface roughness being less than or substantially equal to 2 μm ; disposing a semiconductor die over the first surface of the capping layer through a connecting film, the

connecting film being disposed between the semiconductor die and the capping layer of the first redistribution circuit structure, the semiconductor die being thermally coupled to the metallization layer through the connecting film; and forming a second redistribution circuit structure over the semiconductor die, the second redistribution circuit structure being electrically coupled to the first redistribution circuit structure, and the semiconductor die being disposed between and electrically coupled to the first redistribution circuit structure and the second redistribution circuit structure. [0134] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the disclosure. Those skilled in the art should appreciate that they may readily use the disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the disclosure.

Claims

1. A package structure, comprising: a first redistribution circuit structure, comprising a dielectric structure and a routing structure disposed therein, wherein the dielectric structure comprises a trench exposing the routing structure; a semiconductor die, disposed on and electrically coupled to the first redistribution circuit structure; a connecting film, disposed in the trench and between the semiconductor die and the first redistribution circuit structure, the semiconductor die being thermally coupled to the routing structure through the connecting film; and a second redistribution circuit structure, disposed on and electrically coupled to the semiconductor die, the second redistribution circuit structure being electrically coupled to the first redistribution circuit structure, and the semiconductor die being disposed between the first redistribution circuit structure and the second redistribution circuit structure.
2. The package structure of claim 1, further comprising: a plurality of conductive pillars, disposed on and electrically coupled to the routing structure of the first redistribution circuit structure, the plurality of conductive pillars being next to the semiconductor die and electrically connecting the first redistribution circuit structure and the second redistribution circuit structure; and an insulating encapsulation, encapsulating the plurality of conductive pillars and the semiconductor die, the plurality of conductive pillars penetrating through the insulating encapsulation, wherein a thickness of the insulating encapsulation is less than a sum of a thickness of the connecting film and a thickness of the semiconductor die.
3. The package structure of claim 1, further comprising: a plurality of first conductive terminals, disposed on and electrically coupled to the first redistribution circuit structure, the first redistribution circuit structure being disposed between the semiconductor die and the plurality of first conductive terminals; and a plurality of second conductive terminals, disposed on and electrically coupled to the second redistribution circuit structure, the second redistribution circuit structure being disposed between the semiconductor die and the plurality of second conductive terminals.
4. The package structure of claim 1, wherein the connecting film comprises a thermally conductive adhesive layer having a thermal conductivity being about $0.5 \text{ W}/(\text{m}\cdot\text{K})$ to about $50 \text{ W}/(\text{m}\cdot\text{K})$.
5. The package structure of claim 4, wherein the thermally conductive adhesive layer comprises a thermally conductive filler, and an amount of the thermally conductive filler presented in the thermally conductive adhesive layer is ranging from about 40% to about 95%.
6. The package structure of claim 1, wherein a positioning location of the semiconductor die is within a positioning location of the trench in a vertical projection on the first redistribution circuit structure in a stacking direction of the first redistribution circuit structure and the semiconductor

die.

7. A package structure, comprising: a first redistribution circuit structure, comprising a first metallization layer, a capping layer disposed over the first metallization layer, a second metallization layer and a dielectric layer disposed over the second metallization layer, wherein a first surface of the capping layer has a surface roughness being less than or substantially equal to 2 μm ; a semiconductor die, disposed on the first surface of the capping layer and electrically coupled to the first redistribution circuit structure, wherein the second metallization layer is accessibly revealed by a surface of the dielectric layer facing away from the semiconductor die; and a connecting film, disposed between the semiconductor die and the capping layer of the first redistribution circuit structure, the semiconductor die being thermally coupled to the first metallization layer through the connecting film.

8. The package structure of claim 7, wherein a second surface of the first metallization layer is partially exposed by a plurality of openings formed in the capping layer, wherein the second surface of the first metallization layer is lower than the first surface of the capping layer in a stacking direction of the first redistribution circuit structure and the semiconductor die.

9. The package structure of claim 8, wherein the capping layer comprising a single-layer structure.

10. The package structure of claim 7, wherein the capping layer comprises a first dielectric layer and a second dielectric layer disposed thereon, and the second dielectric layer comprises a trench exposing a surface of the first dielectric layer, wherein the surface of the first dielectric layer comprises the first surface of the capping layer, and wherein a second surface of the first metallization layer is exposed by the surface of the first dielectric layer, and the second surface of the first metallization layer is substantially coplanar to the surface of the first dielectric layer.

11. The package structure of claim 10, wherein a positioning location of the semiconductor die is within a positioning location of the trench in a vertical projection on the first redistribution circuit structure in a stacking direction of the first redistribution circuit structure and the semiconductor die.

12. The package structure of claim 7, further comprising: a second redistribution circuit structure, disposed over and electrically coupled to the semiconductor die, the second redistribution circuit structure being electrically coupled to the first redistribution circuit structure, and the semiconductor die being disposed between the first redistribution circuit structure and the second redistribution circuit structure; a plurality of conductive pillars, disposed on the first metallization layer of the first redistribution circuit structure, the plurality of conductive pillars being next to the semiconductor die and electrically connecting the first redistribution circuit structure and the second redistribution circuit structure; an insulating encapsulation, encapsulating the plurality of conductive pillars and the semiconductor die, the plurality of conductive pillars penetrating through the insulating encapsulation; a plurality of first conductive terminals, disposed on and electrically coupled to the first redistribution circuit structure, the first redistribution circuit structure being disposed between the semiconductor die and the plurality of first conductive terminals; and a plurality of second conductive terminals, disposed on and electrically coupled to the second redistribution circuit structure, the second redistribution circuit structure being disposed between the semiconductor die and the plurality of second conductive terminals.

13. The package structure of claim 7, wherein the connecting film comprises a thermally conductive adhesive layer having a thermal conductivity being about 0.5 W/(m.Math.K) to about 50 W/(m.Math.K).

14. The package structure of claim 13, wherein the thermally conductive adhesive layer comprises a thermally conductive filler, and an amount of the thermally conductive filler presented in the thermally conductive adhesive layer is ranging from about 40% to about 95%.

15. A package structure, comprising: a first redistribution circuit structure, comprising a metallization layer and a capping layer disposed over the metallization layer, wherein a first surface of the capping layer has a surface roughness being less than or substantially equal to 2 μm ; a

semiconductor die, disposed on the first surface of the capping layer; a connecting film, disposed between the semiconductor die and the capping layer of the first redistribution circuit structure, the semiconductor die being thermally coupled to the metallization layer through the connecting film, wherein the connecting film comprises thermally conductive fillers therein; and a second redistribution circuit structure, the semiconductor die being disposed between and electrically coupled to the first redistribution circuit structure and the second redistribution circuit structure.

16. The package structure of claim 15, wherein a second surface of the metallization layer is partially exposed by a plurality of openings formed in the capping layer, wherein the second surface of the metallization layer is lower than the first surface of the capping layer in a stacking direction of the first redistribution circuit structure and the semiconductor die.

17. The package structure of claim 15, wherein the capping layer comprises a first dielectric layer and a second dielectric layer disposed thereon, and the second dielectric layer comprises a trench exposing a surface of the first dielectric layer, wherein the surface of the first dielectric layer comprises the first surface of the capping layer, and wherein a second surface of the metallization layer is exposed by the surface of the first dielectric layer, and the second surface of the metallization layer is substantially coplanar to the surface of the first dielectric layer.

18. The package structure of claim 17, wherein a positioning location of the semiconductor die is within a positioning location of the trench in a vertical projection on the first redistribution circuit structure in a stacking direction of the first redistribution circuit structure and the semiconductor die.

19. The package structure of claim 15, wherein the connecting film comprises a thermally conductive adhesive layer having a thermal conductivity being about $0.5 \text{ W}/(\text{m}\cdot\text{K})$ to about $50 \text{ W}/(\text{m}\cdot\text{K})$.

20. The package structure of claim 19, wherein an amount of the thermally conductive filler presented in the thermally conductive adhesive layer is ranging from about 40% to about 95%.
