

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12403846
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Nagl; Matthias et al.

Decorative part and method for producing same

Abstract

A decorative part and a method for producing a decorative part, wherein the decorative part is in particular a lining part of a motor vehicle. The decorative part has a decorative coat which is provided on the rear side with a reinforcing layer and/or on the visible side with a transparent coating. In order to improve the durability or the optical properties, in particular, of a decorative part provided with a light guide for transilluminating and/or backlighting the decorative coat, the decorative part is post processed by a laser treatment.

Inventors:	Nagl; Matthias (Gottingen, DE), Vetter; Ulrich (Gottingen, DE)
Applicant:	JOYSONQUIN Automotive Systems GmbH (Rutesheim, DE)
Family ID:	84975567
Appl. No.:	17/877998
Filed:	July 31, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230038235 A1	Feb. 09, 2023

Foreign Application Priority Data

DE	102021120154.3	Aug. 03, 2021
----	----------------	---------------

Publication Classification

Int. Cl.: B23K26/354 (20140101); B60Q3/54 (20170101); B60Q3/62 (20170101); B60R13/02 (20060101); B23K101/00 (20060101); B23K101/34 (20060101)

U.S. Cl.:

CPC **B60R13/02** (20130101); **B23K26/354** (20151001); **B60Q3/54** (20170201); **B60Q3/62** (20170201); B23K2101/006 (20180801); B23K2101/34 (20180801)

Field of Classification Search

CPC: B23K (26/354); B60Q (3/54); B60Q (3/62)

USPC: 362/488

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2012/0320615	12/2011	Englert	362/511	N/A
2015/0185391	12/2014	Englert	N/A	G02B 6/0011
2016/0062022	12/2015	Wimmer et al.	N/A	G02B 6/005
2016/0299278	12/2015	Liang	N/A	N/A
2017/0144469	12/2016	Franken	N/A	N/A
2019/0001878	12/2018	Schneider	N/A	G09F 21/049
2019/0061614	12/2018	Neuner	N/A	B60Q 3/20
2019/0346612	12/2018	Herlin	N/A	G02B 6/0031
2020/0231090	12/2019	Weih	N/A	B60Q 3/54
2020/0247314	12/2019	Abel et al.	N/A	N/A
2021/0144872	12/2020	Schenk et al.	N/A	H05K 5/066
2023/0366522	12/2022	Guinn	N/A	B60Q 1/2607

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102791526	12/2011	CN	N/A
204596681	12/2014	CN	N/A
105387408	12/2015	CN	N/A
106457875	12/2016	CN	N/A
106965533	12/2016	CN	N/A
107380089	12/2016	CN	N/A
108227283	12/2017	CN	N/A
207644297	12/2017	CN	N/A
207644298	12/2017	CN	N/A
209581360	12/2018	CN	N/A
110710340	12/2019	CN	N/A
111479723	12/2019	CN	N/A
111520634	12/2019	CN	N/A
102012016147	12/2013	DE	N/A
102014100042	12/2014	DE	N/A
102015107705	12/2014	DE	N/A
202015106328	12/2015	DE	N/A
102015211826	12/2015	DE	N/A
202017105880	12/2017	DE	N/A
102019009164	12/2020	DE	N/A

OTHER PUBLICATIONS

German Search Report, in counterpart application No. 102021120154.3, Dated Apr. 13, 2022, 6 pages. cited by applicant

Office Action in counterpart Chinese patent application No. 202210922287.8 dated Jan. 12, 2025, 7 pages. cited by applicant

Office Action in counterpart Chinese patent application No. 20221092287.8 dated Jul. 26, 2025 with English translation, 14 pages. cited by applicant

Primary Examiner: Raabe; Christopher M

Attorney, Agent or Firm: Fattibene and Fattibene, LLC

Background/Summary

FIELD OF THE INVENTION

(1) The present invention relates to a decorative part, in particular a lining part for a motor vehicle. This decorative part has a decorative layer which is provided on the rear side with a reinforcing layer and/or on the visible side with a transparent cover.

BACKGROUND OF THE INVENTION

(2) The reinforcing layer is usually formed by back injection molding of the decorative layer. The transparent cover on the visible side is also preferably formed by overmolding the decorative layer.

(3) Such a decorative part is known, for example, from DE 10 2012 016 147 A1.

(4) A decorative part within the meaning of the present invention is particularly considered as a lining part, for example for lining the dashboard, the side panels of the doors as well as the center console and possibly also for lining the steering wheel. The decorative part usually has a reinforcing layer which is formed from plastic, is preferably applied to the rear side of the decorative layer by injection molding, and has fastening means, such as fastening pins and the like, by means of which the decorative part can be connected to the supporting structure behind it in the interior of the motor vehicle. The decorative part does not necessarily have a transparent cover that can cover the visible side of the decorative layer and protect it from environmental influences. Such a transparent cover is usually formed by injection molding a transparent plastic against the visible side of the decorative side. A transparent plastic in this sense is usually crystal clear. It can also be smoky or opaque transparent, so that the visible side surface of the decorative layer provided behind the cover is visible from the outside. It is understood that the visible side of the decorative part according to the invention may be formed by the transparent cover or the visible-side surface of the decorative layer.

(5) The decorative layer itself can be single or multilayer. It can be formed by several different materials, which are provided next to each other and/or one behind the other in the surface. The individual layers of the decorative layer can penetrate each other and end at the same level on the visible side or be contoured on the visible side or rear side so that the decorative layer does not form a flat surface on the visible side or rear side.

(6) The decorative layer may be formed as a veneer, textile, metal or plastic layer or films, or may consist of or at least comprise combinations of the aforementioned. The individual elements of the decorative layer can have through-holes and be partially perforated. For example, one element of the decorative layer usually has through-holes in the form of a grid into which the other decorative layer is pressed when the reinforcing layer is back injection molded, so that both elements of the decorative layer are visible; cf. DE 10 2012 016 147 A1.

(7) When producing the decorative part, the decorative layer is usually inserted into an injection

mold and back injection molded with the reinforcing layer on one side, preferably first on the rear side. If realized, the transparent cover is then formed on the visible side by overmolding the still free side of the decorative layer. After demolding, the intermediate product produced in this way is brought to its final contour. For this purpose, the intermediate product is at least partially circumferentially trimmed. Usually, at least the decorative layer is larger than the later decorative part before the decorative part is produced, since the decorative layer is clamped between the two mold halves for overmolding and is thus fixed. Trimming the intermediate product exposes the decorative layer at the edge of the decorative part. This destroys any protection of the decorative layer from environmental influences that may have been provided by the overmolding.

(8) Decorative parts of the aforementioned kind are also partially known as backlit decorative parts. For example, DE 10 2014 100 042 A1 or DE 20 2015 106 328 U1 disclose decorative parts that are provided on the rear side with a light guide element that distributes light on the rear side of the decorative part facing away from the decorative layer in order to backlight the decorative layer over as flat an area as possible. The light can also be introduced laterally via the edge, as suggested by DE 20 2017 105 880. In this context, the configuration of the decorative part can be such that the light is distributed over as flat an area as possible in the plane of the decorative layer, so that the decorative layer is uniformly backlit or transilluminated. Other configurations intend to achieve focused backlighting or light transmission through the decorative layer, which is achieved, for example, by arranging individual light sources and/or light guides on the rear side of the decorative layer. In this context, those skilled in the art strive to emit light from the decorative part only substantially orthogonally to the decorative coat, i.e. to emit the light forward. However, a light-guiding layer within the decorative part can sometimes also emit the light at the edge, which is not always desirable for design reasons.

(9) With regard to protecting individual layers of the decorative part at the edge or suppressing light emission at the edge, it is known to post-process the edge. For example, after trimming the intermediate product, a coating pen is used to apply circumferential protection to the edge so that the layers within the decorative part are also protected from environmental influences at the edge. For higher demands on appearance or protection, a two-component or single-component coating can be applied to the edge by spray application. However, this post-processing requires masking of the decorative surface and, if necessary, of the rear side to prevent contamination of these surfaces with the spray coating. In the case of sensitive decorative surfaces which, for example, form the outer surface of the decorative part without a transparent cover, appropriate masking sometimes cannot be applied successfully. Open-pored decors prevent effective masking. The same applies to surfaces that are not smooth, such as fabric surfaces. The subsequent application of edge protection by means of coating always entails the risk of contamination of the semi-finished product, especially on the visible side, so that rejects are to be feared.

(10) The above-mentioned possibilities of applying coating to the edges can also prevent light emission from the outer circumferential surface of the decorative part. However, the same disadvantages can be seen here as before. Coating sometimes also leads to a longer process time until the final decorative part is produced, since the coatings have to cure after application to the edge.

(11) In the aforementioned prior art, in which a light-guiding layer is formed on the decorative part, there is a need to customize the decorative part.

SUMMARY OF THE INVENTION

(12) The present invention is based on the problem of providing an improved decorative part of the aforementioned kind. In this context, the present invention aims to provide a possibility to improve the edge protection and/or to enable the customization of the decorative part.

(13) In view thereof, the present invention proposes a decorative part with the features described and a method of producing a decorative part with the features.

(14) In the approach according to the invention, the decorative part is post-processed by laser

treatment. Post-processing takes place after the individual layers of the decorative part have been formed and usually after an intermediate product of the decorative part has been trimmed to its final contour. The laser treatment is carried out, for example, along a part circumference, preferably over the entire circumference of the intermediate product. As a result, the edge of the intermediate product is post-processed by laser treatment. If the layers provided on one or both sides for this purpose are formed of plastic or contain plastic, these layers can be melted by the laser in order to seal the end face of the element of the decorative part affected by environmental influences at the edge. During the laser treatment, the melted material(s) can be melted together at the edge and thus bonded. Carbonization of individual or all materials of the decorative part can also take place at the edge, which at least significantly reduces the light transmission of the edge. In particular for the carbonization the laser beam is usually irrigated to a rim or an edge of the decorative part, which edge extends essentially perpendicular to a front surface of the decorative layer. Thus the laser beam is usually irrigated onto the edge of the decorative part in a direction essentially perpendicular to the front surface of the decorative layer. During the carbonization treatment, the decorative part may be moved around a stationary laser beam source for treating the entire edge of the decorative part. Accordingly, the laser beam will treat the entire circumferential wall defining the outer contour of the decorative part.

(15) In this way, the plastic component of the decorative layer in particular is melted to provide an effective edge seal. At the same time, however, the laser can also locally ablate an element of the decorative part which changes its optical quality due to environmental influences, so that this element springs back slightly relative to the edge.

(16) Consequently, the laser treatment results in edge protection. However, treating the edge with a laser also leads to micro-scarring on the surface of the edge, which also has the advantage of preventing squeak and rattle, for example, on non-illuminated components. This problem is currently being countered with an anti-squeak coating that is applied to the edge.

(17) Post-processing by laser treatment also offers the possibility of customizing the decorative part. According to the conception of the present invention, this customization is carried out in particular on the rear side, especially on the rear side of a light guide. Here, lettering, logos, designs or the like can be applied by laser engraving. This laser post-treatment offers the possibility of creating local shading in the area of the light guide, which leads to a corresponding shadow cast on the visible side of the decorative part.

(18) Compared with subsequent coating, laser treatment offers the advantage of a shortened production cycle. There are no drying times for any coating. In addition, the laser can be applied at a precise location so that the masking required for coating can be omitted. Due to its bundling, the laser can be precisely aligned with the edge. There is then no need to worry about the laser beam coupling into the decorative surface and altering or destroying the decorative effect there.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Further details and advantages of the present invention will be apparent from the following description of embodiments in conjunction with the drawing. Therein:

(2) FIG. 1 shows a perspective sectional view of the embodiment;

(3) FIG. 2 shows a top view of the rear side of the light-guiding layer of the embodiment;

(4) FIG. 3 shows a top view of the front side of the light-guiding layer;

(5) FIG. 4 shows an enlarged detail of the view according to FIG. 3;

(6) FIG. 5 shows a longitudinal sectional view through a light guide dome of the embodiment with some beam paths,

(7) FIG. 6 shows a sectional view of a second embodiment, and

(8) FIG. 7 shows a schematic view of the decorative part during post-treatment by laser.

DETAILED DESCRIPTION OF THE INVENTION

(9) FIG. 1 shows a decorative part 2 which is provided with a multilayer decorative coat 4. In the present case, the decorative layer consists of a double overmolded decorative layer 6. A transparent coating 8 is applied by overmolding to the front of the decorative layer 6 as a cover to protect the decorative layer 6. On the opposite rear side of the decorative layer 6, a reinforcing layer 10 is provided by injection molding. During injection molding, the reinforcing layer 10 is formed in one piece with pins 12, which will be discussed in more detail later.

(10) The decorative layer formed in the embodiment has a front surface 14 formed by the coating 8.

(11) A light-guiding layer 16 is arranged on the opposite rear side of the decorative coat 4. This light-guiding layer is provided for backlighting the decorative coat 4.

(12) The light-guiding layer 16 is provided on the rear side with a reflector film 18 forming a reflector layer.

(13) The light-guiding layer 16 is provided between the multilayer decorative coat 4 and a substrate 20, which also serves as a rear side cover and forms fastening pins 22 for fastening the substrate 20 and thus the decorative part 2 to a chassis of a vehicle.

(14) As can be seen in FIG. 1, a light guide in the form of a light guide dome characterized by reference sign 24 extends through the substrate 20. This light guide dome 24 has a column segment 26 and a funnel section 28 and carries an LED as a light element 30 at its free end. While the column segment 26 is formed of solid material and is formed as a slightly conically widening light guide which emits the light generated by the light element 30 substantially at right angles to the decorative coat 4, the funnel section 28 acts as a light guide which deflects the light from this right-angled alignment along a central longitudinal axis L of the light guide dome 24 so that it is emitted parallel to the plane of the light-guiding layer 16 into this layer 16.

(15) The funnel section 28 surrounds a shading element 32, which is provided between the column segment 26 and the decorative coat 4 and is rotationally symmetrical in the present case.

(16) Details of the light guide dome 24 can be seen in FIGS. 2 and 3. FIG. 2 shows a shadow pattern 34 formed at the free end of the column segment 26 by means of laser treatment, against which the LED 30 is placed with its light-emitting surface. This shadow pattern 34 is illuminated by the LED 30. This results in a corresponding shadow pattern on the front surface 14. By laser treatment, for example, a lettering or a logo can be applied, which appears as a corresponding shadow pattern on the front surface 14. This makes it possible to customize the decorative part 2.

(17) FIG. 2 further shows a structural grid 36 provided on the rear side of the light-guiding layer 16 and comprising a plurality of spherical caps with a radius of 1 mm and a height of 0.34 mm. This structural grid 36 serves to emit light in the direction of the decorative coat 4. FIG. 2 further shows longitudinal slits 38, to which corresponding longitudinal slits 40 are cut out on the substrate 20. As FIG. 1 illustrates, the pin 12 protrudes through the longitudinal slits 38, 40, which are to be regarded as pin openings in the sense of the present invention. FIG. 1 shows the pin 12 before hot caulking. After hot caulking, the free end of the pin 12 is plastically deformed and abuts against a locking surface 42 formed on the rear side of the longitudinal slit 40. On the opposite side, the substrate 20 forms a supporting surface 44 against which the flat light-guiding layer 16 abuts over a relatively full area, so that the tensile force caused by the caulked pin 12 does not result in any deformation of the light-guiding layer 16 that could impair the light-guiding properties of the layer 16.

(18) The free end region of the light guide dome 24, formed primarily by the pillar or column segment 26, is hexagonal to optimize color mixing when using an RGB LED as a lighting element.

(19) As FIG. 3 illustrates, the shading element 32 is in the form of an injection-molded funnel which has a plurality of bores 46 distributed around its circumference, each of which tapers off towards the decorative coat 4 in the form of a funnel. The bores 46 serve as apertures that partially absorb and partially transmit and thereby scatter the light emitted from the light guide dome 24

toward the decorative coat **4**, so that it emerges scattered from the shading element **32** on the front surface thereof facing the decorative coat **4**. The shading element **32** has a cone-shaped projection **48** positively coupled to the tapered end portion of the funnel section **28** and positioned centrally with respect to the central longitudinal axis L.

(20) As FIG. **4** illustrates, the shading element **32** extends radially to above a reflector identified by reference sign **50**, which has a crescent-shaped course in top view and is thus provided partly below the shading element **32** and partly radially outside it, and the reflector surface **52** of which extends substantially parallel to the longitudinal center axis L.

(21) The production of the embodiment shown in the Figures is as follows: First, the decorative layer **6** is back injection molded with the reinforcing layer **10** and then overmolded with the coating **8** on the visible side to obtain the decorative coat **4** together with the pins **12**. In parallel, for example, injection molding is used to form the light-guiding layer **16** as a unitary component together with the light guide dome **24**. It is understood that multiple light guide domes **24** may be provided depending on the size of the light-guiding layer **16**. Then, with recessing of a substantial part of the light guide domes **24**, the reflector film **18** is applied against the rear side of the light guide layer **16** and joined thereto, in particular glued. These components are joined to the substrate **20**, which is produced separately by means of injection molding, by aligning the two longitudinal slits **38**, **40** with respect to one another and passing them through with the pin **12**. This is melted to its end projecting beyond the substrate **20**, resulting in a thickened region that abuts against the locking surface **42**. Typically, only then is the LED glued on and wired for power. This wiring can be done via a printed circuit board that electrically connects a plurality of LEDs **30**, and can be provided on the rear side of the substrate **20** and/or abut on the rear side of the substrate **20**.

(22) FIG. **5** shows a sectional view of a light guide dome **24** with beam paths. For example, light rays directed via the column segment **26** reach the reflector **50** and are reflected at its surface. The ray path, identified by reference sign I, strikes the reflector **50** at a relatively acute angle and is reflected by a segment of the structural grid **36** immediately adjacent the funnel section and is emitted through the front surface of the light-guiding layer **16**.

(23) The light beam, identified by reference sign II, strikes the surface of reflector **50** at a relatively obtuse angle and is passed through the light-guiding layer **16** substantially parallel thereto.

(24) The light beam, identified by reference sign III, passes through the bore **46** and is reflected within the bore and emitted in the direction of the decorative layer **6**.

(25) These and other reflection effects result in uniform backlighting of the decorative layer **6**.

(26) In FIG. **6**, reference sign **62** identifies a second decorative coat that forms a visible surface **62a** that can be provided with a transparent layer as a coating, which is not shown. Opposite the visible side surface **62a** is a lamination **64**, which is joined to a rear side surface of the second decorative coat **62** in a first lamination step. In a top view of the embodiment or the visible side **62a**, a first decorative layer **66** is provided behind the first lamination **64**. This first decorative layer **66** is formed as a continuous decorative layer. In the viewing direction behind it, there is a second lamination **68** which connects the first decorative layer **66** to a reinforcing layer **70**.

(27) The second decorative coat **62** is provided with a plurality of through-holes **72**. These through-holes are formed before the reinforcing layer **70** is formed. Before forming the reinforcing layer **70**, the first decorative layer **66** and the second decorative coat **62** each lie on top of one another as a flat decorative layer. The injection molding of the reinforcing layer **70** forces surface portions **74** of the first decorative layer **66** into the through-holes **72**, so that these surface portions **74** lie in the plane of the second decorative coat **62**. This situation is shown in FIG. **6**. As a result of the receding of the first decorative layer **66** in the direction of the through-holes **72**, projections are formed by the material of the reinforcing layer **70** which act as optical lenses and are characterized in the drawing by reference sign **76**. In the embodiment shown, the through-holes **72** have an edge geometry that extends orthogonally from the visible surface. Thus, the through-holes **72** are formed as cylindrical through-holes.

(28) Reference sign **78** indicates a light source that introduces light laterally into the reinforcing layer **70**, which in the embodiment acts as a light guide.

(29) This results in a specific emission of the incident light in the region of the projections **76**. The projections **76** emit a higher proportion of light from the reinforcing layer **70** than flat segments **80**, which are arranged between the projections **76** and extend parallel to the rear side of the second decorative coat **62**. In these regions, this decorative molding has a strictly plane-parallel layered structure in which the layers of the first and second decorative coats **62**, **66** and bonding agent layers **64**, **68** provided therebetween and the flat segments **80** of the reinforcing layer **70** extend parallel to each other.

(30) The projections **76** project from the flat segments **80** with their flank surfaces directed obliquely towards each other.

(31) In FIG. **6**, reference sign **82** identifies an edge protection applied to a circumferential edge **81**, which almost completely surrounds the decorative part **2'**. The laser treatment causes carbonization of at least the plastic reinforcing layer **70**. The edge protection **82** covers the entire edge from the visible side of the second decorative coat **62** to the lower side of the reinforcing layer **70** and accordingly seals all decorative coats **62**, **66** circumferentially. Only in the region of the light source **78** is the edge protection **82** removed by post-treatment, so that the light source **78** can inject light into the reinforcing layer **70**.

(32) FIG. **7** shows an example of production of the edge protection. A robot **84** handles the decorative part **2'** and positions it relative to a fixed laser source **86**, which applies the edge protection **82** by laser post-processing.

(33) As a result of this laser post-processing, light is not emitted from the light-guiding layer. The decorative part **2** is shaded at the edge and does not emit any light at the edge.

LIST OF REFERENCE SIGNS

(34) **2** decorative part **4** decorative coat **6** decorative layer **8** coating **10** reinforcing layer **12** pin **14** front surface **16** light-guiding layer **18** reflector film **20** substrate **22** fastening pin **24** light guide dome **26** column segment **28** funnel section **30** light element/LED **32** shading element **34** shadow pattern **36** structural grid **38** longitudinal slit **40** longitudinal slit **42** locking surface **44** supporting surface **46** bore **48** cone-shaped projection **50** reflector **52** reflector surface **L** center longitudinal axis of the light guide dome **2'** decorative part **62** second decorative coat **62a** visible side surface **64** bonding agent layer/first lamination **66** first decorative coat **68** second lamination/bonding agent layer **70** reinforcing layer **72** through-hole **74** surface portion **76** projection **78** light source **80** flat segment of the reinforcing layer **81** edge **82** edge protection **84** robot **86** laser source

Claims

1. Method for producing a decorative part, in which a decorative coat is provided on a rear side of the decorative part on a light transmitting reinforcing layer, an intermediate product produced in this way is trimmed to produce a final contour having an edge and then laser-processed with a laser directed at the edge forming carbonized material at the edge to reduce light transmission at the edge.
2. Method according to claim 1, wherein the carbonized material forms an edge protection.
3. Method according to claim 1, wherein a light guide provided on the rear side for transilluminating or backlighting the decorative coat is laser-processed.
4. Method according to claim 1, wherein: the laser processing results in light not being emitted from the edge.
5. A method for producing a decorative part comprising the steps of: providing a first decorative coat on a surface of a light transmitting layer of the decorative part forming an intermediate product; trimming the intermediate product producing a final contour having an edge; and processing the final contour with a laser directed at the edge reducing light transmission of the light

transmitting layer at the edge of the final contour of the intermediate product.

6. A method for producing a decorative part as recited in claim 5 wherein: said step of processing the final contour with a laser comprises carbonization of material at the edge.

7. A method for producing a decorative part as recited in claim 5 wherein: the light transmitting layer is a reinforcing layer on a rear side of the decorative part.

8. A method for producing a decorative part as recited in claim 7 further comprising the steps of: laser processing a light guide forming a shadow pattern; and providing the light guide on the rear side of the decorative part, whereby the first decorative coat is capable of being illuminated.

9. A method for producing a decorative part as recited in claim 5 further comprising the steps of: providing a light guide on a rear side of the decorative part for illuminating the first decorative coat; and laser-processing the light guide for applying a shadow pattern.

10. A method for producing a decorative part as recited in claim 5 wherein: said step of processing the final contour with a laser results in light not being emitted from the light transmitting layer at the edge.

11. A method for producing a decorative part as recited in claim 5 further comprising: prior to said step of providing the first decorative coat on the surface and said step of processing the final contour with the laser, forming a second decorative coat having through holes on the first decorative coat; and molding the intermediate product forming projections with the first decorative coat extending into the through holes.

12. A method for producing a decorative part as recited in claim 11 wherein: the intermediate product comprises a light guide and the projections comprise optical lenses.

13. A method for producing a decorative part as recited in claim 12 further comprising the step of: placing a light source adjacent an edge of the intermediate product.

14. A method for producing a decorative part as recited in claim 7 further comprising the step of: providing a transparent coating on a visible side of the decorative part.
