

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12406912
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Noh; Hyung Gyun et al.

Semiconductor package

Abstract

The present disclosure provides a semiconductor package capable of improving performance and reliability. The semiconductor package of the present disclosure includes a first device and a second device that are electrically connected to each other, the first device includes a substrate, a first pad formed on an upper side of the substrate, and a passivation film formed on the upper side of the substrate and formed to surround the first pad, the second device includes a second pad placed to face the first pad, and the first pad has a center pad having a first elastic modulus and an edge pad having a second elastic modulus smaller than the first elastic modulus, the edge pad formed to surround the center pad and to contact the passivation film.

Inventors: Noh; Hyung Gyun (Hwaseong-si, KR), Rhew; Keun-Ho (Seoul, KR), Pae; Sang Woo (Suwon-si, KR), Bae; Jin Soo (Seongnam-si, KR), Choi; Deok-Seon (Hwaseong-si, KR), Choi; Il-Joo (Anyang-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 84977304

Assignee: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Appl. No.: 17/591144

Filed: February 02, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230029151 A1	Jan. 26, 2023

Foreign Application Priority Data

KR	10-2021-0095686	Jul. 21, 2021
----	-----------------	---------------

Publication Classification

Int. Cl.: H01L23/498 (20060101); H01L23/14 (20060101); H01L23/532 (20060101)

U.S. Cl.:

CPC H01L23/49811 (20130101); H01L23/14 (20130101); H01L23/53228 (20130101);

Field of Classification Search

CPC: H01L (23/49811); H01L (24/08); H01L (24/02); H01L (24/15)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8349649	12/2012	Kurita	N/A	N/A
9224681	12/2014	Ebefors et al.	N/A	N/A
9396998	12/2015	Kurita et al.	N/A	N/A
9673172	12/2016	Maydar et al.	N/A	N/A
10170399	12/2018	Ho et al.	N/A	N/A
2017/0133333	12/2016	Kim	N/A	H01L 24/05
2021/0057036	12/2020	Khan	N/A	H01L 25/18
2021/0104482	12/2020	Hong	N/A	H01L 24/14
2021/0125955	12/2020	Suh et al.	N/A	N/A
2021/0375790	12/2020	Oda	N/A	H01L 24/80

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
H08-153752	12/1995	JP	N/A
2015090891	12/2014	JP	N/A
10-1178840	12/2011	KR	N/A

Primary Examiner: Fan; Michele

Attorney, Agent or Firm: Muir Patent Law, PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This application claims priority to Korean Patent Application No. 10-2021-0095686 filed on Jul. 21, 2021 in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. 119, the contents of which in its entirety are herein incorporated by reference.

BACKGROUND

1. Field of the Disclosure

(2) The present disclosure relates to a semiconductor package. More specifically, the present disclosure relates to a decrease in thermal stress of a passivation film using a stress relaxation pad (an edge pad).

2. Description of the Related Art

(3) The interposer market is growing by a demand of a high specification of set and an adoption of high bandwidth memory (HBM). For example, in the case of a semiconductor package that uses a silicon-based interposer, the semiconductor package may be fabricated by surface-mounting a semiconductor chip on the silicon-based interposer, and by molding the mounted semiconductor chip with a molding material.

(4) On the other hand, due to the high specification of set in the recent years, the number of high-bandwidth memories has increased, and the size of semiconductor packages has enlarged. This induces problems that increase a stress caused by a difference in coefficient of thermal expansion (CTE), increase the process difficulty of the semiconductor package, and decrease the yield.

SUMMARY

(5) Aspects of the present disclosure provide a semiconductor package capable of improving performance and reliability.

(6) However, aspects of the present disclosure are not restricted to the one set forth herein. The above and other aspects of the present disclosure will become more apparent to one of ordinary skill in the art to which the present disclosure pertains by referencing the detailed description of the present disclosure given below.

(7) According to an aspect of the present disclosure, there is provided a semiconductor package comprising, a first device and a second device that are electrically connected to each other, wherein the first device includes a substrate, a first pad formed on an upper side of the substrate, and a passivation film formed on the upper side of the substrate and formed to surround the first pad, the second device includes a second pad placed to face the first pad, and the first pad has a center pad having a first elastic modulus and an edge pad having a second elastic modulus smaller than the first elastic modulus, the edge pad formed to surround the center pad and to contact the passivation film.

(8) According to another aspect of the present disclosure, there is provided a semiconductor package comprising, an interposer substrate, and a semiconductor chip which is mounted on the interposer substrate and electrically connected to the interposer substrate, wherein the interposer substrate includes an interposer, a passivation film which is in contact with an upper side of the interposer, an interposer pad which penetrates the passivation film and is electrically connected to a redistribution layer inside the interposer, and a stress relaxation pad which penetrates the passivation film and surrounds the interposer pad, and wherein an upper side of the interposer pad is located on the same plane as an upper side of the stress relaxation pad.

(9) According to another aspect of the present disclosure, there is provided a semiconductor package comprising, a circuit board, an interposer substrate on the circuit board, and a logic semiconductor chip and a memory semiconductor chip mounted on the interposer substrate and electrically connected to the interposer substrate, wherein the interposer substrate includes an interposer, an interposer pad which is placed on an upper side of the interposer and includes a conductive material, a stress relaxation pad which is placed on the upper side of the interposer, surrounds a periphery of the interposer pad, and includes an insulating material, and a passivation film which surrounds a periphery of the stress relaxation pad, on the upper side of the interposer, wherein a width of the stress relaxation pad is 1 μm or more and 10 μm or less.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The above and other aspects and features of the present disclosure will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings, in which:

- (2) FIG. 1 is an exemplary diagram for explaining a semiconductor package according to some embodiments.
- (3) FIG. 2 is a graph showing a relationship between a width of the edge pad of FIG. 1 and a thermal stress of the passivation film.
- (4) FIGS. 3 to 6 are exemplary diagrams for explaining semiconductor packages according to some embodiments.
- (5) FIGS. 7 to 10 are exemplary plan views for explaining edge pads according to some embodiments.
- (6) FIG. 11 is a schematic layout diagram for explaining a semiconductor package according to some embodiments.
- (7) FIG. 12 is a cross-sectional view taken along A-A of FIG. 11.
- (8) FIG. 13 is an enlarged view for explaining a region P of FIG. 12.
- (9) FIG. 14 is a diagram for explaining a semiconductor package according to some embodiments.
- (10) FIG. 15 is an enlarged view for explaining a region Q of FIG. 14.
- (11) FIG. 16 is a diagram for explaining a semiconductor package according to some embodiments.
- (12) FIG. 17 is an enlarged view for explaining a region R of FIG. 16.
- (13) FIG. 18 is a diagram for explaining a semiconductor package according to some embodiments.
- (14) FIG. 19 is an enlarged view for explaining a region S of FIG. 18.
- (15) FIG. 20 is an exemplary layout diagram of a semiconductor package according to some embodiments.
- (16) FIG. 21 is an exemplary layout diagram of a semiconductor package according to some embodiments.
- (17) FIG. 22 is an exemplary layout diagram of a semiconductor package according to some embodiments.
- (18) FIG. 23 is a cross-sectional view taken along a line B-B of FIG. 22.

DETAILED DESCRIPTION OF THE EMBODIMENTS

- (19) Hereinafter, semiconductor packages according to some embodiments will be described referring to FIGS. 1 to 23.
- (20) FIG. 1 is an exemplary diagram for explaining a semiconductor package according to some embodiments. FIG. 2 is a graph showing a relationship between a width of the edge pad of FIG. 1 and a thermal stress of the passivation film.
- (21) Referring to FIGS. 1 and 2, the semiconductor package according to some embodiments may include a first device 10 and a second device 20.
- (22) The first device 10 and the second device 20 may be electrically connected to each other. For example, the first device 10 and the second device 20 may be electrically connected to each other through a first pad 13, a second pad 23, and a solder bump 35. Each of the first device 10 and the second device 20 may be, for example, a circuit board, an interposer, a logic semiconductor chip, or a memory semiconductor chip.
- (23) As used herein, components described as being “electrically connected” are configured such that an electrical signal can be transferred from one component to the other (although such electrical signal may be attenuated in strength as it transferred and may be selectively transferred).
- (24) The first device 10 may include a substrate 11, a passivation film 12, a first pad 13, and a redistribution layer/pattern 14. Although not shown, the first device 10 may include an insulating layer, and may also include through electrodes.
- (25) The substrate 11 may include or may be, for example, at least one of a silicon-based interposer, a circuit board, a logic semiconductor chip, and a memory semiconductor chip. In the present specification, the substrate 11 will be described as including a silicon-based interposer.
- (26) The first pad 13 may be formed on the substrate 11. The first pad 13 may be placed on an upper side (or a top/upper surface) 11_US of the substrate 11. The first pad 13 may come into contact with the upper side 11_US of the substrate 11.

(27) It will be understood that when an element is referred to as being “connected” or “coupled” to or “on” another element, it can be directly connected or coupled to or on the other element or intervening elements may be present. In contrast, when an element is referred to as being “directly connected” or “directly coupled” to another element, or as “contacting” or “in contact with” another element, there are no intervening elements present at the point of contact.

(28) The second pad **23** may be placed to face the first pad **13**. The first device **10** and the second device **20** may be electrically connected to each other, using the first pad **13** and the second pad **23**. The second pad **23** may include or be formed of, for example, but is not limited to, metallic materials such as copper (Cu) or aluminum (Al). The contents of the first pad **13** will be described later.

(29) In some embodiments, the first pad **13** may include a center pad **13C** and an edge pad **13E**. The edge pad **13E** may be formed to surround the center pad **13C**. The center pad **13C** may include or be formed of a conductive material. For example, the center pad **13C** may include or be formed of, but is not limited to, metallic materials such as copper (Cu) or aluminum (Al).

(30) The edge pad **13E** may include or be formed of an insulating material. The edge pad **13E** may include or be formed of an oxide-based insulating material. For example, the edge pad **13E** may be formed of, but is not limited to, tetraethyl ortho silicate (TEOS) or photo-sensitive polyimide (PSPI). The edge pad **13E** may be formed of a material capable of relieving the thermal stress of the passivation film **12** to be described later.

(31) The edge pad **13E** may have a width **W1** in a first direction **X**. The width **W1** of the edge pad **13E** may be 1 μm or more and 20 μm or less. For example, the width **W1** of the edge pad **13E** may be 1 μm or more and 10 μm or less. For example, the width **W1** of the edge pad **13E** may be 5 μm or more and 10 μm or less.

(32) The edge pad **13E** may vertically overlap the solder bump **35**. For example, the edge pad **13E** may completely overlap the solder bump **35** in the second direction **Z**. As used herein, the first direction **X** may be a horizontal direction. The second direction **Z** may be a vertical direction. The first direction **X** and the second direction **Z** may be perpendicular to each other. However, the technical idea of the present disclosure is not limited thereto.

(33) In FIG. 2, an x-axis means/represents a width of the edge pad **13E** in the first direction **X**. A y-axis means/represents a thermal stress of the passivation film **12**. For example, the width of the edge pad **13E** may be a distance from a surface of the edge pad **13E** contacting the center pad **13C** to a surface of the edge pad **13E** positioned in a direction receding from a center of the center pad **13C** and contacting the passivation film **12**.

(34) When the edge pad **13E** is not formed, e.g., when the width of the edge pad **13E** is 0 μm , the thermal stress of the passivation film **12** is defined as 1.

(35) When the width **W1** of the edge pad **13E** is 1 μm , the thermal stress of the passivation film **12** is 0.92. The thermal stress of the passivation film **12**, when the width **W1** of the edge pad **13E** is 1 μm , may be reduced by about 8% as compared to a case where the edge pad **13E** is not formed (when the width of the edge pad **13E** is 0 μm).

(36) When the width **W1** of the edge pad **13E** is 5 μm , the thermal stress of the passivation film **12** is 0.82. The thermal stress of the passivation film **12**, when the width **W1** of the edge pad **13E** is 5 μm , may be reduced by about 18% as compared to a case where the edge pad **13E** is not formed (when the width of the edge pad **13E** is 0 μm).

(37) When the width **W1** of the edge pad **13E** is 10 μm , the thermal stress of the passivation film **12** is 0.64. The thermal stress of the passivation film **12**, when the width **W1** of the edge pad **13E** is 10 μm , may be reduced by about 36% compared to a case where the edge pad **13E** is not formed (when the width of the edge pad **13E** is 0 μm).

(38) When the width **W1** of the edge pad **13E** is 15 μm , the thermal stress of the passivation film **12** is 0.6. The thermal stress of the passivation film **12**, when the width **W1** of the edge pad **13E** is 15 μm , may be reduced by about 40% compared to a case where the edge pad **13E** is not formed

(when the width of the edge pad **13E** is 0 μm).

(39) When the width **W1** of the edge pad **13E** is 20 μm , the thermal stress of the passivation film **12** is 0.58. The thermal stress of the passivation film **12**, when the width **W1** of the edge pad **13E** is 20 μm , may be reduced by about 42% compared to a case where the edge pad **13E** is not formed (when the width of the edge pad **13E** is 0 μm).

(40) The center pad **13C** may have a first modulus. The edge pad **13E** may have a second modulus. The term “modulus” is a mechanical property that measures the stiffness of a solid material. The modulus is a modulus of elasticity that defines a relationship between stress and strain of a linear elastic material in a uniaxial deformation region. In general, a material having a high modulus may be a material having a high rigidity. For example, the first modulus and the second modulus may be elastic modulus or Young's modulus of the center pad **13C** and the edge pad **13E**.

(41) In some embodiments, the first modulus of the center pad **13C** may be greater than the second modulus of the edge pad **13E**. For example, the rigidity of the center pad **13C** may be greater than the rigidity of the edge pad **13E**. The thermal stress of the passivation film **12** may be relaxed, using a difference between rigidity of the center pad **13C** and rigidity of the edge pad **13E**.

(42) The second modulus of the edge pad **13E** may be, for example, but is not limited to, greater than 15 GPa and smaller than 117 GPa.

(43) The edge pad **13E** may relax the thermal stress of the passivation film **12**. The coefficient of thermal expansion of the edge pad **13E** may be 1 ppm/K or more and 17 ppm/K or less. For example, the edge pad **13E** may be a material capable of relieving the thermal stress of the passivation film **12**, while having a coefficient of thermal expansion of 1 ppm/K or more and 17 ppm/K or less.

(44) The passivation film **12** may be formed on the substrate **11**. The passivation film **12** may be placed on the upper side **11_US** of the substrate **11**. The passivation film **12** may come into contact with the upper side **11_US** of the substrate **11**. The passivation film **12** may be formed to surround the first pad **13**. The passivation film **12** may come into contact with the edge pad **13E**. The passivation film **12** may not come into contact with the center pad **13C**.

(45) The passivation film **12** may be, for example, but is not limited to, a silicon nitride film/layer. For example, the passivation film **12** may include or be formed of a nitride-based insulating material. The passivation film **12** may be made up of a passivation material, BCB (benzocyclobutene), polybenzeneoxazole, polyimide, epoxy, silicon oxide, silicon nitride, or a combination thereof.

(46) In some embodiments, a height of the center pad **13C** in the second direction **Z** may be the same as a height of the edge pad **13E** in the second direction **Z**. An upper side (a top/upper surface) **13C_US** of the center pad **13C** may be located on the same plane as an upper side (a top/upper surface) **13E_US** of the edge pad **13E**. A height of the passivation film **12** in the second direction **Z** may be the same as the heights of the center pad **13C** and the edge pad **13E** in the second direction **Z**. An upper side (a top/upper surface) **12_US** of the passivation film **12** may be located on the same plane as the upper side **13C_US** of the center pad **13C** and the upper side **13E_US** of the edge pad **13E**.

(47) The redistribution layer/pattern **14** may be formed inside the substrate **11**. The redistribution layer **14** may be electrically connected to the first pad **13**. The redistribution layer **14** may be electrically connected to the center pad **13C**. The redistribution layer **14** may include or be formed of a conductive material. The redistribution layer **14** may include or be formed of, for example, but is not limited to, at least one of copper (Cu), aluminum (Al), silver (Ag), tin (Sn), gold (Au), nickel (Ni), lead (Pb), titanium (Ti), and alloys thereof.

(48) The semiconductor package according to some embodiments may further include a solder bump **35** and an underfill **30**.

(49) The first device **10** and the second device **20** may be electrically connected to each other through the solder bump **35**. The first pad **13** and the second pad **23** may be electrically connected

to each other through the solder bump **35**.

(50) The solder bump **35** may electrically connect the first device **10** and the second device **20**. The solder bump **35** may include or be formed of solder material. The solder bump **35** may include or be formed of, for example, but is not limited to, at least one of lead (Pb), tin (Sn), indium (In), bismuth (Bi), antimony (Sb), silver (Ag), and alloys thereof.

(51) The underfill **30** may be formed between the first device **10** and the second device **20**. The underfill **30** may fill a space between the first device **10** and the second device **20**. Also, the underfill **30** may cover the solder bump **35**. For example, the underfill **30** may surround and contact side surfaces of solder bumps **35**. The underfill **30** may include or be formed of, for example, but is not limited to, an insulating polymeric material such as an EMC (epoxy molding compound).

(52) FIGS. **3** to **6** are exemplary diagrams for explaining a semiconductor package according to some embodiments. For convenience of explanation, points/aspects different from those described using FIGS. **1** and **2** will be mainly described.

(53) Referring to an embodiment illustrated in FIG. **3**, as shown in the cross-section, the width/distance between the outer sides of the edge pad **13E** in the first direction X may be the same as a width of the solder bump **35** in the first direction X. The outer side of the edge pad **13E** may be a portion that comes into contact with the passivation film **12**. In this case, the edge pad **13E** completely overlaps the solder bump **35** in the second direction Z.

(54) Referring to an embodiment illustrated in FIG. **4**, as shown in the cross-section, the width between the outer sides of the edge pad **13E** in the first direction X may be greater than the width of the solder bump **35** in the first direction X.

(55) For example, the edge pad **13E** may include a portion that does not overlap the solder bump **35** in the second direction Z.

(56) Referring to an embodiment illustrated in FIG. **5**, the edge pad **13E** may not be symmetrical from the viewpoint of the cross-section.

(57) The edge pad **13E** may include a first edge pad **13E1** and a second edge pad **13E2**. The first edge pad **13E1** and the second edge pad **13E2** may be respectively placed on one side and the other side of the center pad **13C**.

(58) A width W2 of the first edge pad **13E1** in the first direction X may be different from a width W3 of the second edge pad **13E2** in the first direction X. Although the width W2 of the first edge pad **13E1** in the first direction X is shown as being greater than the width W3 of the second edge pad **13E2** in the first direction X, the embodiment is not limited thereto. The width W3 of the second edge pad **13E2** in the first direction X may be greater than the width W2 of the first edge pad **13E1** in the first direction X in certain embodiments.

(59) A part of the first edge pad **13E1** may not overlap the solder bump **35** in the second direction Z. The second edge pad **13E2** may completely overlap the solder bump **35** in the second direction Z. However, the technical idea of the present disclosure is not limited thereto. In certain embodiments, the first edge pad **13E1** and the second edge pad **13E2**, while the width W2 of the first edge pad **13E1** in the first direction X is different from the width W3 of the second edge pad **13E2** in the first direction X, both the first edge pad **13E1** and the second edge pad **13E2** may completely overlap the solder bump **35** in the second direction Z.

(60) In certain embodiments, the first edge pad **13E1** and the second edge pad **13E2** may have portions that do not overlap the solder bump **35** in the second direction Z, while the width W2 of the first edge pad **13E1** in the first direction X is different from the width W3 of the second edge pad **13E2** in the first direction X.

(61) Referring to FIG. **6**, the second pad **23** and the first pad **13** may come into contact with each other. For example, the second pad **23** and the center pad **13C** may be bonded to each other. In this case, the solder bump **35** may not be included. Although the widths of the second pad **23** and the center pad **13C** in the first direction X are shown as being the same as each other, the embodiment is not limited thereto.

(62) FIGS. 7 to 10 are exemplary plan views for explaining an edge pad according to some embodiments. The edge pad according to some embodiments will be described in more detail using FIGS. 7 to 10.

(63) Referring to FIGS. 7 to 10, the center pad 13C may have a circular shape, e.g., in a plan view. Although the center pad 13C is shown as being placed in a zigzag shape in the drawings, the embodiment is not limited thereto.

(64) The edge pad 13E may be formed around the center pad 13C. The edge pad 13E may come into contact with the center pad 13C. The edge pad 13E may include an inner side 13E_a and an outer side 13E_b. The inner side 13E_a of the edge pad 13E may be a side that comes into contact with the center pad 13C. The outer side 13E_b of the edge pad 13E may be opposite to the inner side 13E_a of the edge pad 13E. The outer side 13E_b of the edge pad 13E may come into contact with the passivation film 12. The edge pad 13E may be placed between the center pad 13C and the passivation film 12. The redistribution layer 14 may overlap the center pad 13C.

(65) In FIG. 7, the outer side 13E_b of the edge pad 13E may have a circular shape, e.g., in a plan view. In this case, the width of the edge pad 13E may be the same in a cross-section.

(66) In FIG. 8, the outer side 13E_b of the edge pad 13E may have a square shape, e.g., in a plan view. In this case, the width of the edge pad 13E may differ depending on position and/or on direction, e.g., in a plan view.

(67) In FIG. 9, the outer side 13E_b of the edge pad 13E may have a hexagonal shape, e.g., in a plan view. In this case, the width of the edge pad 13E may differ depending on position and/or on direction, e.g., in a plan view.

(68) In FIG. 10, the outer side 13E_b of the edge pad 13E may have a triangular shape, e.g., in a plan view. In this case, the width of the edge pad 13E may differ depending on position and/or on direction, e.g., in a plan view.

(69) In the present specification, although the outer side 13E_b of the edge pad 13E is shown to include one of a circular shape, a square shape, a hexagonal shape and a triangular shape, the embodiment is not limited thereto. The outer side 13E_b of the edge pad 13E may have various shapes, e.g., in a plan view. For example, the outer side 13E_b of the edge pad 13E may be a circle, a quadrangle, a triangle, or a hexagon in a plan view.

(70) FIG. 11 is a schematic layout diagram for explaining a semiconductor package according to some embodiments. FIG. 12 is a cross-sectional view taken along A-A of FIG. 11. FIG. 13 is an enlarged view for explaining a region P of FIG. 12. Hereinafter, the semiconductor package including the edge pad described using FIGS. 1 to 10 will be described.

(71) In FIGS. 11 to 13, the semiconductor package according to some embodiments may be a 2.5D package including a silicon interposer. However, this is only an example, and the technical idea of the present disclosure is not limited thereto.

(72) Referring to FIGS. 11 to 13, the semiconductor package according to some embodiments may include a circuit board 100, an interposer structure 200, a first semiconductor chip 310, a second semiconductor chip 320, and a molding member 400.

(73) The interposer structure 200 may be mounted on the circuit board 100. A first semiconductor chip 310 and a second semiconductor chip 320 may be mounted on the interposer structure 200. The first semiconductor chip 310 and the second semiconductor chip 320 may be placed apart from each other in the first direction X. Second semiconductor chips 320 may be placed on one side and the other side of the first semiconductor chip 310. Two or more second semiconductor chips 320 may be arranged in the third direction Y. The second semiconductor chips 320 may be spaced apart from each other in the third direction Y. The third direction Y may be perpendicular to the first direction X and the second direction Z.

(74) The circuit board 100 may be a packaging board. The circuit board 100 may be a printed circuit board (PCB). The circuit board 100 may include an upper side (e.g., a top/upper surface) and a lower side (e.g., a bottom/lower surface) that are opposite to each other.

(75) The circuit board **100** may include an insulating core **101**, a first board pad **102**, and a second board pad **104**. For example, the circuit board **100** may include a plurality of first board pads **102**, and a plurality of second board pads **104**. The first board pads **102** and the second board pads **104** may be used to electrically connect the circuit board **100** to other components. For example, the first board pad **102** may be exposed from the lower surface/side of the insulating core **101**, and the second board pad **104** may be exposed from the upper surface/side of the insulating core **101**. The first board pad **102** and the second board pad **104** may include or be formed of, but are not limited to, metallic materials such as, for example, copper (Cu) or aluminum (Al).

(76) Wiring patterns for electrically connecting the first board pad **102** and the second board pad **104** may be formed inside the insulating core **101**. Although the insulating core **101** is shown as a single layer, this is only for convenience of explanation. For example, it is a matter of course that an insulating core **101** is made up of multiple layers in certain embodiments, and multi-layered wiring patterns may be formed inside the insulating core **101**.

(77) The circuit board **100** may be mounted on a motherboard or the like of an electronic device. For example, a first connecting member **150** electrically connected to the first board pad **102** may be formed. The circuit board **100** may be mounted on a motherboard or the like of an electronic device through the first connecting member **150**. The circuit board **100** may be, but is not limited to, a BGA (Ball Grid Array board).

(78) The first connecting member **150** may be, for example, but is not limited to, a solder bump. The first connecting member **150** may have various shapes such as a land, a ball, a pin, and a pillar. It is a matter of course that the number, gap, arrangement form, and the like of the first connecting member **150** are not limited to those shown and may differ depending on the design.

(79) In some embodiments, the insulating core **101** may include or be formed of an organic matter. For example, the insulating core **101** may include or be formed of a pre-preg. The pre-preg is a composite fiber in which reinforcing fibers such as carbon fiber, glass fiber, and aramid fiber are impregnated with a thermosetting polymer binder (e.g., epoxy resin) or a thermoplastic resin in advance.

(80) In some embodiments, the circuit board **100** may include or may be a copper clad laminate (CCL). For example, the circuit board **100** may have a structure in which a copper laminate is stacked on one side or both sides of a thermosetting pre-preg (e.g., pre-preg of a C-Stage).

(81) The interposer structure **200** may be placed on the upper surface/side of the circuit board **100**. The interposer structure **200** may be, for example, but is not limited to, a silicon interposer. The interposer structure **200** may include a lower side (e.g., a bottom/lower surface) and an upper side (e.g., a top/upper surface) that are opposite to each other. The interposer structure **200** facilitates the electrical connection between the circuit board **100** and first and second semiconductor chips **310** and **320** to be described later, and may prevent warpage of the semiconductor package.

(82) The interposer structure **200** may include a first interposer pad **202** and a second interposer pad **204**. The first interposer pad **202** and the second interposer pad **204** may be used to electrically connect the interposer structure **200** to other components, respectively. For example, the first interposer pad **202** may be exposed from the lower side/surface of the interposer structure **200**, and the second interposer pad **204** may be exposed from the upper side/surface of the interposer structure **200**. The first interposer pad **202** and the second interposer pad **204** may include or be formed of, for example, but are not limited to, metallic materials such as copper (Cu) or aluminum (Al). Wiring patterns for electrically connecting the first interposer pad **202** and the second interposer pad **204** may be formed inside the interposer structure **200**.

(83) The interposer structure **200** may be mounted on the upper side/surface of the circuit board **100**. For example, a second connecting member **250** may be formed/disposed between the circuit board **100** and the interposer structure **200**. The second connecting member **250** may electrically connect the second board pad **104** and the first interposer pad **202**. Accordingly, the circuit board **100** and the interposer structure **200** may be electrically connected through the second connecting

member **250**.

(84) The second connecting member **250** may be, but is not limited to, a solder bump including a low-melting point metal, for example, tin (Sn), tin (Sn) alloy or the like. The second connecting member **250** may have various shapes such as a land, a ball, a pin, and a pillar. The second connecting member **250** may be formed of a single layer or multiple layers. When the second connecting member **250** is formed of a single layer, the second connecting member **250** may include or be formed of, for example, tin-silver (Sn—Ag) solder or copper (Cu). When the second connecting member **250** is formed of multiple layers, the second connecting member **250** may include, for example, a copper (Cu) filler and solder. It is a matter of course that the number, gap, arrangement form, and the like of the second connecting member **250** are not limited to those shown in the drawings and may vary depending on the design.

(85) In some embodiments, the interposer structure **200** may be an interposer substrate and may include an interposer **210**, a through via **240**, and a redistribution layer **230**.

(86) The interposer **210** may be, for example, but is not limited to, a silicon film. The through via **240** may be placed inside the interposer **210**. For example, the through via **240** may be placed inside the interposer **210** and electrically connected to the first interposer pad **202**.

(87) In some embodiments, a first underfill **260** may be formed between the circuit board **100** and the interposer structure **200**. The first underfill **260** may fill a space between the circuit board **100** and the interposer structure **200**. Further, the first underfill **260** may cover the second connecting member **250**. For example, the first underfill **260** may surround and contact side walls of second connecting members **250**. The first underfill **260** may prevent the interposer structure **200** from being broken or the like by fixing the interposer structure **200** onto the circuit board **100**. The first underfill **260** may include or be formed of, for example, but is not limited to, an insulating polymeric material such as an EMC (epoxy molding compound).

(88) In some embodiments, the interposer structure **200** may include a passivation film **220** and a stress relaxation pad **205**. The stress relaxation pad **205** may be, for example, the edge pad **13E** of FIG. **1**. For example, the stress relaxation pad **205** may relax the thermal stress of the passivation film **220**.

(89) The stress relaxation pad **205** may be formed on the upper side/surface **210 US** of the interposer **210**. The stress relaxation pad **205** may be placed around the second interposer pad **204**. The stress relaxation pad **205** may surround the second interposer pad **204**. The stress relaxation pad **205** may come into contact with the second interposer pad **204**. The inner side of the stress relaxation pad **205** may come into contact with the second interposer pad **204**. For example, a plurality of stress relaxation pads **205** may respectively surround and contact side surfaces of the second interposer pads **204**.

(90) The passivation film **220** may extend on the upper side/surface **210 US** of the interposer **210**. The passivation film **220** may come into contact with the stress relaxation pad **205**. The outer side of the stress relaxation pad **205** may come into contact with the passivation film **220**. For example, the passivation film **220** may surround and contact side surfaces of the stress relaxation pads **205**. The stress relaxation pad **205** and the second interposer pad **204** may each penetrate the passivation film **220**, e.g., in the second direction **Z**, and come into contact with the upper side/surface **210 US** of the interposer **210**.

(91) When the semiconductor package according to some embodiment is exposed to a high temperature, the thermal stress may be concentrated on the passivation film **220**. The second connecting member **250** may have a higher coefficient of thermal expansion (CTE) than the passivation film **220**. The thermal stress may be concentrated on the passivation film **220** due to a difference in the coefficient of thermal expansion between the second connecting member **250** and the passivation film **220**.

(92) The stress relaxation pad **205** of the semiconductor package according to some embodiments of the present disclosure may be placed between the second interposer pads **204** and the passivation

film **220** to relax the thermal stress of the passivation film **220**.

(93) The stress relaxation pad **205** may be the edge pad **13E** described in FIG. **1**. The stress relaxation pad **205** may include or be formed of an insulating material. The stress relaxation pad **205** may include or be formed of, for example, TEOS or PSPI.

(94) In a cross-section, a width **W1** of the stress relaxation pad **205** in the first direction **X** may be 1 μm or more and 20 μm or less. For example, the width **W1** of the stress relaxation pad **205** in the first direction **X** may be 1 μm or more and 10 μm or less. For example, the width **W1** of the stress relaxation pad **205** in the first direction **X** may be 5 μm or more and 10 μm or less. The coefficient of thermal expansion of the stress relaxation pad **205** may be 1 ppm/K or more and 17 ppm/K or less. The modulus of the stress relaxation pad **205** may be smaller than the modulus of the second interposer pad **204**. For example, the modulus of the stress relaxation pad **205** may be greater than 15 GPa and smaller than 117 GPa. However, the technical idea of the present disclosure is not limited thereto.

(95) In a plan view, the stress relaxation pad **205** may include an inner side that comes into contact with the second interposer pad **204**, and an outer side that comes into contact with the passivation film **220**. The outer side of the stress relaxation pad **205** may have a circular shape, a square shape, a triangular shape or a hexagonal shape. However, the technical idea of the present disclosure is not limited thereto.

(96) The passivation film **220** may be, for example, but is not limited to, a silicon nitride film. The passivation film **220** may also be formed of a passivation material, BCB (benzocyclobutene), polybenzeneoxazole, polyimide, epoxy, silicon oxide, silicon nitride or a combination thereof in certain embodiments.

(97) An upper side/surface **205_US** of the stress relaxation pad **205** may be located on the same plane as the upper side/surface **204_US** of the second interposer pad **204**. The upper side/surface **205_US** of the stress relaxation pad **205** may be located on the same plane as the upper side/surface **220_US** of the passivation film **220**. The upper side/surface **205_US** of the stress relaxation pad **205**, the upper side/surface **204_US** of the second interposer pad **204**, and the upper side/surface **220_US** of the passivation film **220** may be/constitute the upper side/surface of the interposer structure **200**.

(98) The first semiconductor chip **310** and the second semiconductor chip **320** may be spaced apart from each other in the first direction **X** and placed on the upper side/surface of the interposer structure **200**. The first semiconductor chip **310** and the second semiconductor chip **320** may each be an integrated circuit (IC) in which hundreds to millions or more of semiconductor elements are integrated in a single chip.

(99) In some embodiments, the first semiconductor chip **310** may be a logic semiconductor chip. For example, the first semiconductor chip **310** may be, for example, but is not limited to, an application processor (AP), such as a CPU (Central Processing Unit), a GPU (Graphic Processing Unit), an FPGA (Field-Programmable Gate Array), a digital signal processor, an encryption processor, a microprocessor, a microcontroller, and an ASIC (Application-Specific IC).

(100) In some embodiments, the second semiconductor chip **320** may be a memory semiconductor chip. For example, the second semiconductor chip **320** may be a volatile memory such as a DRAM (dynamic random access memory) or an SRAM (static random access memory), or may be a non-volatile memory such as a flash memory, a PRAM (Phase change Random Access Memory), a MRAM (Magnetoresistive Random Access Memory), a FeRAM (Ferroelectric Random Access Memory) or a RRAM (Resistive Random Access Memory).

(101) As an example, the first semiconductor chip **310** may be an ASIC such as a GPU, and the second semiconductor chip **320** may be a stack memory such as a high bandwidth memory (HBM). Such a stack memory may have a form in which a plurality of integrated circuits are stacked. The stacked integrated circuits may be electrically connected to each other through a TSV (Through Silicon Via) or the like.

(102) In some embodiments, the number of second semiconductor chips **320** may be provided more than the number of first semiconductor chips **310**. For example, a plurality of second semiconductor chips **320** may be placed around the first semiconductor chip **310**. As an example, as shown in FIG. **11**, two second semiconductor chips **320** may each be placed on both sides of the first semiconductor chip **310**.

(103) The first semiconductor chip **310** may include a first chip pad **312**. The first chip pad **312** may be used to electrically connect the first semiconductor chip **310** to other components. For example, the first chip pad **312** may be exposed from the lower side/surface of the first semiconductor chip **310**.

(104) The second semiconductor chip **320** may include a second chip pad **314**. The second chip pad **314** may be used to electrically connect the second semiconductor chip **320** to other components. For example, the second chip pad **314** may be exposed from the lower side/surface of the second semiconductor chip **320**.

(105) The first chip pad **312** and the second chip pad **314** may each include or be formed of, for example, but are not limited to, a metallic material such as copper (Cu) or aluminum (Al).

(106) The first semiconductor chip **310** and the second semiconductor chip **320** may be mounted on the upper side/surface of the interposer structure **200**. For example, a third connecting member **352** may be formed/disposed between the interposer structure **200** and the first semiconductor chip **310**. The third connecting member **352** may electrically connect some of the plurality of second interposer pads **204** to the first chip pad **312**. For example, the third connecting member **352** may contact some of the plurality of second interposer pads **204** and the first chip pad **312**. Accordingly, the interposer structure **200** and the first semiconductor chip **310** may be electrically connected to each other.

(107) Further, for example, a fourth connecting member **354** may be formed/disposed between the interposer structure **200** and the second semiconductor chip **320**. The fourth connecting member **354** may electrically connect some others of the plurality of second interposer pads **204** to the second chip pad **314**. For example, the fourth connecting member **354** may contact some others of the plurality of second interposer pads **204** and the second chip pad **314**. Accordingly, the interposer structure **200** and the second semiconductor chip **320** may be electrically connected.

(108) In some embodiments, a part of the redistribution layer **230** may electrically connect the third connecting member **352** and the fourth connecting member **354**. For example, a part of the redistribution layer **230** may electrically connect the second interposer pad **204** connected to the third connecting member **352** with the second interposer pad **204** electrically connected to the fourth connecting member **354**. Accordingly, the first semiconductor chip **310** and the second semiconductor chip **320** may be electrically connected.

(109) The third connecting member **352** and the fourth connecting member **354** may each be, but are not limited to, a solder bump including low melting point metals, for example, tin (Sn) and tin (Sn) alloys. The third connecting member **352** and the fourth connecting member **354** may have various shapes such as a land, a ball, a pin, and a pillar. The third connecting member **352** and the fourth connecting member **354** may include or may be, but are not limited to, a UBM (Under Bump Metallurgy).

(110) In some embodiments, a second underfill **362** may be formed between the interposer structure **200** and the first semiconductor chip **310**, and a third underfill **364** may be formed between the interposer structure **200** and the second semiconductor chip **320**. The second underfill **362** may fill a space between the interposer structure **200** and the first semiconductor chip **310**, and the third underfill **364** may fill a space between the interposer structure **200** and the second semiconductor chip **320**. Further, the second underfill **362** may cover the third connecting member **352**, and the third underfill **364** may cover the fourth connecting member **354**. For example, the second underfill **362** may surround and contact side surfaces of third connecting members **352**, and the third underfill **364** may surround and contact side surfaces of fourth connecting members **354**.

The second underfill **362** and the third underfill **364** may prevent the first and second semiconductor chips **310** and **320** from being broken, by fixing the first and second semiconductor chips **310** and **320** onto the interposer structure **200**. The second underfill **362** and the third underfill **364** may each include or be formed of, for example, but are not limited to, an insulating polymeric material such as an EMC.

(111) The molding member **400** may be formed on the upper side (top/upper surface) of the interposer structure **200**. The molding member **400** may be formed to cover at least a part of the first and second semiconductor chips **310** and **320**. For example, the molding member **400** may cover/contact the side faces of the first semiconductor chip **310**, the side faces of the second semiconductor chip **320**, the second underfill **362** and the third underfill **364**. Although the molding member **400** is only shown as exposing the upper side (top/upper surface) of the first semiconductor chip **310** and the upper side (top/upper surface) of the second semiconductor chip **320**, this is merely an example, and the molding member **400** may, of course, cover the upper side (top/upper surface) of the first semiconductor chip **310** and the upper side (top/upper surface) of the second semiconductor chip **320**.

(112) The molding member **400** may include or be formed of, but is not limited to, an insulating polymeric material such as an EMC. In some embodiments, the first underfill **260**, the second underfill **362** and the third underfill **364** may include or be formed of materials different from the molding member **400**. For example, the first underfill **260**, the second underfill **362**, and the third underfill **364** may each include or be formed of an insulating material having fluidity that is superior to the molding member **400**. Accordingly, the first underfill **260**, the second underfill **362**, and the third underfill **364** may efficiently fill the narrow space between the circuit board **100** and the interposer structure **200**, or between the interposer structure **200** and the first and second semiconductor chips **310** and **320**.

(113) FIG. **14** is a diagram for explaining a semiconductor package according to some embodiments. FIG. **15** is an enlarged view for explaining a region Q of FIG. **14**. For convenience of explanation, features/points different from those described using FIGS. **11** to **13** will be mainly described.

(114) Referring to FIGS. **14** and **15**, the stress relaxation pad **205** may not be placed around the second interposer pad **204** electrically connected to the first semiconductor chip **310**.

(115) In some embodiments, the second interposer pad **204** may include a second_1 interposer pad **204_1** and a second_2 interposer pad **204_2**.

(116) The second_1 interposer pad **204_1** may be a second interposer pad **204** electrically connected to the first semiconductor chip **310**. The second_2 interposer pad **204_2** may be a second interposer pad **204** electrically connected to the second semiconductor chip **320**. The second_1 interposer pad **204_1** may be electrically connected to and/or contact the third connecting member **352**. The second_1 interposer pad **204_1** may be electrically connected to the first chip pad **312**, e.g., through the third connecting member **352**. The second_2 interposer pad **204_2** may be electrically connected to and/or contact the fourth connecting member **354**. The second_2 interposer pad **204_2** may be electrically connected to the second chip pad **314**, e.g., through the fourth connecting member **354**.

(117) The stress relaxation pad **205** may not be placed around the second_1 interposer pad **204_1**. The stress relaxation pad **205** may not be placed around the second_1 interposer pad **204_1** which is the second interposer pad **204** electrically connected to the first semiconductor chip **310**. For example, the stress relaxation pad **205** may not be formed around the second interposer pad **204** electrically connected to the logic semiconductor chip.

(118) The stress relaxation pad **205** may be placed around the second_2 interposer pad **204_2**. The stress relaxation pad **205** may be placed around the second_2 interposer pad **204_2** which is the second interposer pad **204** electrically connected to the second semiconductor chip **320**. For example, the stress relaxation pad **205** may be formed around the second interposer pad **204**

electrically connected to the memory semiconductor chip.

(119) FIG. **16** is a diagram for explaining a semiconductor package according to some embodiments. FIG. **17** is an enlarged view for explaining a region R of FIG. **16**. For convenience of explanation, features/points different from those described using FIGS. **11** to **15** will be mainly described.

(120) Referring to FIGS. **16** and **17**, the stress relaxation pad **205** may not be placed around the second_2 interposer pad **204_2**.

(121) The stress relaxation pad **205** may not be placed around the second_2 interposer pad **204_2**. The stress relaxation pad **205** may not be placed around the second_2 interposer pad **204_2** which is the second interposer pad **204** electrically connected to the second semiconductor chip **320**. For example, the stress relaxation pad **205** may not be formed around the second interposer pad **204** electrically connected to the logic semiconductor chip.

(122) The stress relaxation pad **205** may be placed around the second_1 interposer pad **204_1**. The stress relaxation pad **205** may be placed around the second_1 interposer pad **204_1** which is the second interposer pad **204** electrically connected to the first semiconductor chip **310**. For example, the stress relaxation pad **205** may be formed around the second interposer pad **204** electrically connected to the memory semiconductor chip.

(123) FIG. **18** is a diagram for explaining a semiconductor package according to some embodiments. FIG. **19** is an enlarged view for explaining a region S of FIG. **18**. For convenience of explanation, features/points different from those described using FIGS. **11** to **13** will be mainly described.

(124) Referring to FIGS. **18** and **19**, the interposer **210** may be multiple layers. For example, the interposer **210** may include a semiconductor film **211** and an interlayer insulating film **213**.

(125) The semiconductor film **211** may be, for example, but is not limited to, a silicon film. The through via **240** may penetrate the semiconductor film **211**. For example, the through via **240** may extend from the top/upper surface/side of the semiconductor film **211** and be electrically connected to and/or contact the first interposer pad **202**.

(126) The interlayer insulating film **213** may cover the top/upper side/surface of the semiconductor film **211**. The interlayer insulating film **213** may include or be formed of, for example, but is not limited to, at least one of silicon oxide, silicon nitride, silicon oxynitride, and low-k materials having a lower dielectric constant than silicon oxide. The redistribution layer **230** may be formed inside the interlayer insulating film **213**. The redistribution layer **230** may electrically connect the through via **240** to the second interposer pad **204**.

(127) FIG. **20** is an exemplary layout diagram of a semiconductor package according to some embodiments. For convenience of explanation, features/points different from those described using FIGS. **11** to **13** will be mainly described.

(128) Referring to FIG. **20**, in the semiconductor package according to some embodiments, six second semiconductor chips **320** may be placed around the first semiconductor chip **310**.

(129) For example, the second semiconductor chips **320** may be placed side by side in the third direction Y on one side of the first semiconductor chip **310**. The second semiconductor chips **320** may be placed side by side in the third direction Y on the other side of the first semiconductor chip **310**. For example, six memory semiconductor chips may be placed around the single logic semiconductor chip.

(130) FIG. **21** is an exemplary layout diagram of the semiconductor package according to some embodiments. For convenience of explanation, features/points different from those described using FIGS. **11** to **13** will be mainly described.

(131) Referring to FIG. **21**, the semiconductor package according to some embodiments may include a dummy chip **330**.

(132) The dummy chip **330** may not function as the semiconductor chip. For example, the dummy chip **330** may not function as an integrated circuit chip. The dummy chip **330** may be arranged

with, for example, the first semiconductor chips **310** along the first direction X. As an example, as shown in FIG. **21**, two first semiconductor chips **310** may each be placed on both sides of the dummy chip **330**. For example, the dummy chips **330** may be disposed on both sides of the first semiconductor chips **310**. For example, each of the dummy chips **330** may be disposed between two second semiconductor chips **320** in the third direction Y.

(133) FIG. **22** is an exemplary layout diagram of the semiconductor package according to some embodiments. FIG. **23** is a cross-sectional view taken along a line B-B of FIG. **22**. For convenience of explanation, features/points different from those described using FIGS. **11** to **13** will be mainly described.

(134) In FIGS. **22** and **23**, the semiconductor package according to some embodiments may be a 3D package including a silicon interposer. However, this is merely an example, and the technical idea of the present disclosure is not limited thereto.

(135) Referring to FIGS. **22** and **23**, the semiconductor package according to some embodiments may include a circuit board **100**, an interposer structure **200**, a first semiconductor chip **310**, and a second semiconductor chip **320**.

(136) In some embodiments, the first semiconductor chip **310** and the second semiconductor chip **320** may be stacked sequentially. The first semiconductor chip **310** may be spaced apart from the second semiconductor chip **320** in the second direction Z. For example, the second semiconductor chip **320** may be formed/disposed on the first semiconductor chip **310**. At least one or more second semiconductor chips **320** may be provided. In FIG. **23**, a second_1 semiconductor chip **321** and a second_2 semiconductor chip **323** may be sequentially stacked on the first semiconductor chip **310**. Although the two second semiconductor chips **320** are shown, this is merely for convenience of explanation, and the embodiment is not limited thereto.

(137) The circuit board **100** may be a packaging board. The circuit board **100** may be a printed circuit board (PCB). The circuit board **100** may include an insulating core **101**, a first board pad **102** and a second board pad **104**.

(138) The circuit board **100** may be mounted on a motherboard or the like of an electronic device. For example, a first connecting member **150** electrically connected to and/or in contact with the first board pad **102** may be formed/disposed on a bottom surface of the circuit board **100**. The circuit board **100** may be mounted on a motherboard or the like of an electronic device through the first connecting member **150**.

(139) The interposer structure **200** may be placed on the upper/top side/surface of the circuit board **100**. The interposer structure **200** may be, for example, but is not limited to, a silicon interposer.

(140) The interposer structure **200** may be mounted on the upper/top side/surface of the circuit board **100**. For example, a second connecting member **250** may be formed/disposed between the circuit board **100** and the interposer structure **200**. The second connecting member **250** may electrically connect the second board pad **104** and the first interposer pad **202**. Accordingly, the circuit board **100** and the interposer structure **200** may be electrically connected, e.g., through the second connecting member **250**.

(141) In some embodiments, a first underfill **260** may be formed between the circuit board **100** and the interposer structure **200**. The first underfill **260** may fill the space between the circuit board **100** and the interposer structure **200**.

(142) The interposer structure **200** may include an interposer **210**, and a passivation film **220**, a second interposer pad **204** and a stress relaxation pad **205** placed on the upper/top side/surface of the interposer **210**. The stress relaxation pad **205** may be placed between the second interposer pad **204** and the passivation film **220**. The stress relaxation pad **205** may relax the thermal stress of the passivation film **220**.

(143) The first semiconductor chip **310** may be placed on the upper/top side/surface of the interposer structure **200**. The first semiconductor chip **310** may be a logic semiconductor chip. For example, the first semiconductor chip **310** may be, but is not limited to, an application processor

(AP), such as a CPU (Central Processing Unit), a GPU (Graphic Processing Unit), an FPGA (Field-Programmable Gate Array), a digital signal processor, an encryption processor, a microprocessor, a microcontroller, and an ASIC (Application-Specific IC).

(144) The first semiconductor chip **310** may include a third chip pad **302** and a fourth chip pad **304**. The third chip pad **302** and the fourth chip pad **304** may each be used to electrically connect the first semiconductor chip **310** to other components. For example, the third chip pad **302** may be exposed from the lower/bottom side/surface of the first semiconductor chip **310**. The fourth chip pad **304** may be exposed from the upper/top side/surface of the first semiconductor chip **310**.

(145) The third chip pad **302** and the fourth chip pad **304** may each include or be formed of, for example, but are not limited to, a metallic material such as copper (Cu) or aluminum (Al).

(146) In some embodiments, a fifth connecting member **351** may be formed/disposed between the interposer structure **200** and the first semiconductor chip **310**. The fifth connecting member **351** may electrically connect the second interposer pad **204** and the third chip pad **302**. Accordingly, the interposer structure **200** and the first semiconductor chip **310** may be electrically connected to each other, e.g., through the fifth connecting member **351**.

(147) The fifth connecting member **351** may be, but is not limited to, a solder bump including or formed of a low melting point metal, for example, tin (Sn) and tin (Sn) alloy. The fifth connecting member **351** may have various shapes such as a land, a ball, a pin, and a pillar. The fifth connecting member **351** may include, but is not limited to, a UBM (Under Bump Metallurgy).

(148) In some embodiments, a fourth underfill **361** may be formed between the interposer structure **200** and the first semiconductor chip **310**. The fourth underfill **361** may fill the space between the interposer structure **200** and the first semiconductor chip **310**. The fourth underfill **361** may cover the fifth connecting member **351**. For example, the fourth underfill **361** may surround and contact side surfaces of fifth connecting members **351**. The fourth underfill **361** may prevent the first semiconductor chip **310** from being broken or the like by fixing the first semiconductor chip **310** onto the interposer structure **200**. The fourth underfill **361** may include or be formed of, but is not limited to, one or more insulating polymeric materials such as an EMC.

(149) The second semiconductor chips **320** may be placed on the upper/top side/surface of the first semiconductor chip **310**. The second semiconductor chips **320** may include a second_1 semiconductor chip **321** and a second_2 semiconductor chip **323**. The second_1 semiconductor chip **321** may be mounted on the upper/top side/surface of the first semiconductor chip **310**. The second_2 semiconductor chip **323** may be mounted on the upper/top side/surface of the second_1 semiconductor chip **321**.

(150) Each of the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323** may be a memory semiconductor chip. For example, the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323** may each be a volatile memory such as a DRAM (dynamic random access memory) or an SRAM (static random access memory), or may be a non-volatile memory such as a flash memory, a PRAM (Phase-change Random Access Memory), a MRAM (Magnetoresistive Random Access Memory), a FeRAM (Ferroelectric Random Access Memory) or a RRAM (Resistive Random Access Memory).

(151) The second_1 semiconductor chip **321** may include a fifth chip pad **306** and a sixth chip pad **308**. Each of the fifth chip pad **306** and the sixth chip pad **308** may be used to electrically connect the second_1 semiconductor chip **321** to other components. For example, the fifth chip pad **306** may be exposed from the lower/bottom side/surface of the second_1 semiconductor chip **321**. The sixth chip pad **308** may be exposed from the upper/top side/surface of the second_1 semiconductor chip **321**.

(152) The fifth chip pad **306** and the sixth chip pad **308** may each include or be formed of, for example, but are not limited to, one or more metallic materials such as copper (Cu) or aluminum (Al).

(153) In some embodiments, a sixth connecting member **353** may be formed/disposed between the

first semiconductor chip **310** and the second_1 semiconductor chip **321**. The sixth connecting member **353** may electrically connect the fourth chip pad **304** and the fifth chip pad **306**. Accordingly, the first semiconductor chip **310** and the second_1 semiconductor chip **321** may be electrically connected, e.g., through the sixth connecting member **353**.

(154) The sixth connecting member **353** may be, but is not limited to, a solder bump including a low melting point metal, for example, a tin (Sn) and tin (Sn) alloy. The sixth connecting member **353** may have various shapes such as a land, a ball, a pin, and a pillar. The sixth connecting member **353** may include, but is not limited to, a UBM (Under Bump Metallurgy).

(155) In some embodiments, a fifth underfill **363** may be formed between the first semiconductor chip **310** and the second_1 semiconductor chip **321**. The fifth underfill **363** may fill the space between the first semiconductor chip **310** and the second_1 semiconductor chip **321**. The fifth underfill **363** may cover the sixth connecting member **353**. For example, the fifth underfill **363** may surround and contact side surfaces of the sixth connecting member **353**. The fifth underfill **363** may prevent the second_1 semiconductor chip **321** from being broken or the like by fixing the second_1 semiconductor chip **321** onto the first semiconductor chip **310**. The fifth underfill **363** may include or be formed of, but is not limited to, an insulating polymeric material such as an EMC.

(156) The second_2 semiconductor chip **323** may include a seventh chip pad **309**. The seventh chip pad **309** may be used to electrically connect the second_2 semiconductor chip **323** to other components. For example, the seventh chip pad **309** may be exposed from the lower/bottom side/surface of the second_2 semiconductor chip **323**. The seventh chip pad **309** may include or be formed of, but is not limited to, one or more metallic materials such as copper (Cu) or aluminum (Al).

(157) In some embodiments, a seventh connecting member **355** may be formed/disposed between the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323**. The seventh connecting member **355** may electrically connect the sixth chip pad **308** and the seventh chip pad **309**. Accordingly, the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323** may be electrically connected to each other, e.g., through the seventh connecting member **355**.

(158) The seventh connecting member **355** may be, but is not limited to, a solder bump including or formed of a low melting point metal, for example, tin (Sn) and tin (Sn) alloys. The seventh connecting member **355** may have various shapes such as a land, a ball, a pin, and a pillar. The seventh connecting member **355** may include, but is not limited to, an UBM (Under Bump Metallurgy).

(159) In some embodiments, a sixth underfill **365** may be formed between the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323**. The sixth underfill **365** may fill the space between the second_1 semiconductor chip **321** and the second_2 semiconductor chip **323**. The sixth underfill **365** may cover the seventh connecting member **355**. For example, the sixth underfill **365** may surround and contact side surface of the seventh connecting member **355**. The sixth underfill **365** may prevent the second_2 semiconductor chip **323** from being broken or the like by fixing the second_2 semiconductor chip **323** onto the second_1 semiconductor chip **321**. The sixth underfill **365** may include or be formed of, for example, but is not limited to, an insulating polymeric material such as an EMC.

(160) In concluding the detailed description, those skilled in the art will appreciate that many variations and modifications may be made to the preferred embodiments without substantially departing from the principles of the present disclosure. Therefore, the disclosed preferred embodiments of the disclosure are used in a generic and descriptive sense only and not for purposes of limitation.

Claims

1. A semiconductor package comprising: a first device and a second device that are electrically connected to each other, wherein the first device includes a substrate, a first pad formed on an upper side of the substrate, and a passivation film formed on the upper side of the substrate and formed to surround the first pad, the second device includes a second pad placed to face the first pad, and the first pad has a center pad having a first elastic modulus and an edge pad having a second elastic modulus smaller than the first elastic modulus, the edge pad formed to surround the center pad and to directly contact the passivation film, wherein an upper side of the center pad, an upper side of the edge pad, and an upper side of the passivation film are located on the same plane, wherein a lower side of the center pad, a lower side of the edge pad, and a lower side of the passivation film are located on the same plane, and wherein the first pad and the second pad are electrically connected to each other through a solder bump.
2. The semiconductor package of claim 1, wherein a width of the edge pad in a horizontal direction between the center pad and the passivation film is 1 μm or more and 10 μm or less.
3. The semiconductor package of claim 1, wherein the center pad includes a conductive material, and the edge pad includes an insulating material.
4. The semiconductor package of claim 3, wherein the edge pad includes an oxide-based insulating material, and the passivation film includes a nitride-based insulating material.
5. The semiconductor package of claim 1, wherein the edge pad includes an inner side that comes into contact with the center pad, and an outer side opposite to the inner side, and a shape of the outer side is a circle, a quadrangle, a triangle, or a hexagon.
6. The semiconductor package of claim 1, wherein in cross-section, the edge pad includes a first edge pad and a second edge pad respectively placed on one side and the other side of the center pad, and a width of the first edge pad is different from a width of the second edge pad.
7. The semiconductor package of claim 6, further comprising: a solder bump which electrically connects the first pad and the second pad, the first edge pad completely overlaps the solder bump in a vertical direction, and the second edge pad includes a portion which does not overlap the solder bump in the vertical direction.
8. A semiconductor package comprising: an interposer substrate; and a semiconductor chip which is mounted on the interposer substrate and electrically connected to the interposer substrate, wherein the interposer substrate includes an interposer, a passivation film which is in contact with an upper side of the interposer, an interposer pad which penetrates the passivation film and is electrically connected to a redistribution layer inside the interposer, and a stress relaxation pad which penetrates the passivation film and surrounds the interposer pad, and wherein an upper side of the interposer pad is located on the same plane as an upper side of the stress relaxation pad.
9. The semiconductor package of claim 8, wherein a width of the stress relaxation pad is 1 μm or more and 10 μm or less.
10. The semiconductor package of claim 8, wherein an elastic modulus of the stress relaxation pad is greater than 15 GPa and smaller than 117 GPa.
11. The semiconductor package of claim 8, wherein a coefficient of thermal expansion of the stress relaxation pad is 1 ppm/K or more and 17 ppm/K or less.
12. The semiconductor package of claim 8, wherein the stress relaxation pad includes an inner side that is in contact with the interposer pad, and an outer side opposite to the inner side, a shape of the outer side is a circle, a quadrangle, a triangle, or a hexagon.
13. A semiconductor package comprising: a circuit board; an interposer substrate on the circuit board; and a logic semiconductor chip and a memory semiconductor chip mounted on the interposer substrate and electrically connected to the interposer substrate, wherein the interposer substrate includes an interposer, an interposer pad which is placed on an upper side of the interposer and includes a conductive material, a stress relaxation pad which is placed on the upper side of the interposer, surrounds a periphery of the interposer pad, and includes an insulating

material, and a passivation film which surrounds a periphery of the stress relaxation pad, on the upper side of the interposer, wherein a width of the stress relaxation pad is 1 μm or more and 10 μm or less, wherein an upper side of the interposer pad is located on the same plane as an upper side of the stress relaxation pad, and wherein a lower side of the interposer pad is located on the same plane as a lower side of the stress relaxation pad.

14. The semiconductor package of claim 13, wherein the logic semiconductor chip and the memory semiconductor chip are spaced apart from each other in a horizontal direction, and the semiconductor package further comprises a molding member placed between the logic semiconductor chip and the memory semiconductor chip.

15. The semiconductor package of claim 14, wherein the interposer substrate includes a first interposer pad electrically connected to the logic semiconductor chip, and a second interposer pad electrically connected to the memory semiconductor chip, and the first interposer pad or the second interposer pad is not surrounded by a stress relaxation pad.

16. The semiconductor package of claim 13, wherein the logic semiconductor chip and the memory semiconductor chip are spaced apart from each other in a vertical direction, and the logic semiconductor chip is placed between the interposer substrate and the memory semiconductor chip.
