

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12406938
B2
September 02, 2025
Chen; Wen-Yen et al.

Methods of forming alignment structure with trenches for semiconductor devices

Abstract

A method of forming a semiconductor device is provided. The method includes providing a substrate having a first region and a second region; forming a plurality of trenches in the first region of the substrate; forming a multi-layer stack over the substrate and in the trenches; and patterning the multi-layer stack and the substrate to form first nanostructures over first fins in the first region and second nanostructures over second fins in the second region, where the multi-layer stack includes at least one of first semiconductor layers and at least one of second semiconductor layer stacked alternately, and the plurality of trenches are in corresponding ones of the first fins.

Inventors: Chen; Wen-Yen (Hsinchu, TW), Huang; Tsai-Yu (Taoyuan, TW), Chang; Huicheng (Tainan, TW), Yeo; Yee-Chia (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Family ID: 84365141

Assignee: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Appl. No.: 17/689413

Filed: March 08, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230050645 A1	Feb. 16, 2023

Related U.S. Application Data

us-provisional-application US 63232755 20210813

Publication Classification

Int. Cl.: H01L23/544 (20060101); H01L21/02 (20060101); H01L21/324 (20060101); H10D30/01 (20250101); H10D30/67 (20250101); H10D62/10 (20250101); H10D64/01 (20250101)

U.S. Cl.:

CPC H01L23/544 (20130101); H01L21/0259 (20130101); H01L21/3247 (20130101); H10D30/031 (20250101); H10D30/6735 (20250101); H10D30/6757 (20250101); H10D62/118 (20250101); H10D64/017 (20250101); H01L2223/54426 (20130101)

Field of Classification Search

CPC: H01L (23/544); H01L (21/0259); H10D (30/024); H10D (30/62)

USPC: 257/347

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9209247	12/2014	Colinge et al.	N/A	N/A
9236267	12/2015	De et al.	N/A	N/A
9412817	12/2015	Yang et al.	N/A	N/A
9412828	12/2015	Ching et al.	N/A	N/A
9472618	12/2015	Oxland	N/A	N/A
9502265	12/2015	Jiang et al.	N/A	N/A
9520482	12/2015	Chang et al.	N/A	N/A
9536738	12/2016	Huang et al.	N/A	N/A
9576814	12/2016	Wu et al.	N/A	N/A
9608116	12/2016	Ching et al.	N/A	N/A
2009/0079002	12/2008	Lee et al.	N/A	N/A
2016/0307850	12/2015	Lin et al.	N/A	N/A
2019/0043993	12/2018	Mohapatra et al.	N/A	N/A
2020/0219760	12/2019	Kantarovsky	N/A	H01L 21/302
2022/0139783	12/2021	Gardner	438/154	H01L 29/66439

Primary Examiner: Hoang; Quoc D

Attorney, Agent or Firm: Slater Matsil, LLP

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE (1) This application claims the benefit of U.S. Provisional Application No. 63/232,755, Filed on Aug. 13, 2021 and entitled “Zero Layer Lithography Overlay Reflection Position Accuracy by Depositing SiGe Nanosheet into Alignment Mark,” which application is hereby incorporated herein by reference.

BACKGROUND

(1) Semiconductor devices are used in a variety of electronic applications, such as personal computers, cell phones, digital cameras, and other electronic equipment. Semiconductor devices are typically fabricated by sequentially depositing insulating or dielectric layers, conductive layers and semiconductor layers over a semiconductor substrate and patterning the various layers using lithography to form circuit components and elements thereon.

(2) The semiconductor industry continues to improve the integration density of various electronic components (e.g., transistors, diodes, resistors, capacitors, etc.) by continual reductions in minimum feature size, which allow more components to be integrated into a given area. However, as the minimum feature sizes are reduced, additional problems arise that should be addressed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The present disclosure is best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 illustrates a top view of a semiconductor device in accordance with some embodiments.

(3) FIG. 2 illustrates an example of nano-FETs in a three-dimensional view in accordance with some embodiments.

(4) FIGS. 3A, 4A, 6A, 7A, 8A, 9A, 10A, 11, 12A, 13A, 14A, 15A, 16A, 17, 18A, 19A, 3B, 4B, 6B, 7B, 8B, 9B, 10B, 12B, 13B, 14B, 15B, 16B, 18B, 19B, and 20 are cross-sectional views of intermediate stages in the manufacturing of nano-FETs in accordance with some embodiments.

(5) FIG. 5 is a top view of an alignment structure in accordance with some embodiments.

DETAILED DESCRIPTION

(6) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(8) FIG. 1 illustrates a top view of a semiconductor device **100** in accordance with some embodiments. In some embodiments, the semiconductor device **100** includes a wafer **101**. The wafer **101** may include a plurality of chip regions **102** (or referred as to active regions) separated from each other by dicing regions **103**. In some embodiments, each of the chip regions **102** may include a semiconductor device. Such semiconductor device may include a transistor such as nano-

FETs, FinFETs, other multi-gate transistors, planar transistors, bipolar junction transistors, or other types of devices such as resistors, capacitors, inductors, diodes, fuses, static random-access memory (SRAM), and/or other logic circuits, etc. The dicing regions **103** may also be referred to as singulation regions or isolation regions. In some embodiments, the wafer **101** may be singulated along the dicing regions **103** to separate the chip regions **102** from each other and form individual chips. In some embodiments, the semiconductor device **100** further includes alignment structures **105** disposed in the dicing regions **103**. In some embodiments, the alignment structures **105** may be disposed at an edge of the wafer **101**. In other embodiments, the alignment structures **105** may be disposed at corners of the chip regions **102**. In yet other embodiments, the alignment structures **105** may be disposed at edges of the chip regions **102**. The alignment structures **105** may also be referred to as alignment marks. In some embodiments, when the alignment structures **105** are formed in the dicing regions **103**, the alignment structures **105** may be damaged or destroyed by the singulation process.

(9) In some embodiments, each of the chip regions **102** includes one or more chips. For example, in the embodiments illustrated in FIG. 1, each of the chip regions **102** includes four chips, such as chips **102A**, **102B**, **102C**, and **102D**. In other embodiments, each of the chip regions **102** may include less or more than four chips depending on the design requirements. In some embodiments, when each of the chip regions **102** includes a plurality of chips, the alignment structures **105** may be disposed within the chip regions **102** between adjacent chips. In such embodiments, the alignment structures **105** are not damage or destroyed during the singulation process and retain in the final products.

(10) FIG. 2 illustrates an example of nano-FETs (e.g., nanowire FETs, nanosheet FETs, or the like) in a three-dimensional view, in accordance with some embodiments. The nano-FETs include nanostructures **55** (e.g., nanosheets, nanowire, or the like) over fins **50** on a substrate **10** (e.g., a semiconductor substrate), wherein the nanostructures **55** act as channel regions for the nano-FETs. The nanostructures **55** may include P-type nanostructures, N-type nanostructures, or a combination thereof. Isolation features **62** are disposed between adjacent fins **50**, which may protrude above and between neighboring isolation features **62**. Although the isolation features **62** are described/illustrated as being separate from the substrate **10**, as used herein, the term “substrate” may refer to the semiconductor substrate alone or a combination of the semiconductor substrate and the isolation regions. Additionally, although a bottom portion of the fins **50** is illustrated as being single, continuous materials with the substrate **10**, the bottom portion of the fins **50** and/or the substrate **10** may include a single material or a plurality of materials. In this context, fins **50** refer to the portion extending between the neighboring isolation features **62**.

(11) Gate dielectric layer **90** are over top surfaces of the fins **50** and along top surfaces, sidewalls, and bottom surfaces of the nanostructures **55**. Gate electrodes **92** are over the gate dielectric layers **90**. Source/drain features **80** are disposed over the fins **50** on opposing sides of the gate dielectric layers **90** and the gate electrodes **92**.

(12) FIGS. 3A through 19B are cross-sectional views of intermediate stages in the manufacturing of nano-FETs in the chip regions and the dicing regions, in accordance with some embodiments. FIGS. 3A, 4A, 6A through 10A, 11, 12A through 16A, 18A, and 19A illustrate reference cross-section A-A' illustrated in the chip region **102**. The cross-section A-A' is along a longitudinal axis of the gate electrodes **92** and in a direction, for example, perpendicular to a direction of a current flow between the source/drain features **80** of the nano-FETs illustrated in FIG. 2. FIG. 17 illustrates reference cross-section B-B' illustrated in the chip region **102**. The cross-section B-B is parallel to cross-section A-A' and extends through the source/drain features **80** of the nano-FETs illustrated in FIG. 2. FIGS. 3B, 4B, 6B through 10B, 12B through 16B, 18B, and 19B illustrate reference cross-section C-C' illustrated in the dicing region **103**. The cross-section C-C' is along a direction that is parallel to the cross-section A-A' and extends through the dicing region **103**.

(13) Referring to FIGS. 3A and 3B, a substrate **10** having a chip region **102** and a dicing region **103**

is provided. The substrate **10** may be a semiconductor substrate, such as a bulk semiconductor, a semiconductor-on-insulator (SOI) substrate, or the like, which may be doped (e.g., with a P-type or an N-type dopant) or undoped. The substrate **10** may be a wafer, such as a silicon wafer. Generally, an SOI substrate is a layer of a semiconductor material formed on an insulator layer. The insulator layer may be, for example, a buried oxide (BOX) layer, a silicon oxide layer, or the like. The insulator layer is provided on a substrate, typically a silicon or glass substrate. Other substrates, such as a multi-layered or gradient substrate, may also be used. In some embodiments, the semiconductor material of the substrate **10** may include silicon; germanium; a compound semiconductor including silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including silicon-germanium, gallium arsenide phosphide, aluminum indium arsenide, aluminum gallium arsenide, gallium indium arsenide, gallium indium phosphide, and/or gallium indium arsenide phosphide; or combinations thereof.

(14) Referring to FIGS. **4A** and **4B**, a first mask layer **12** is formed over the substrate **10**, in accordance with some embodiments. A second mask layer **14** is formed over the first mask layer **12**, in accordance with some embodiments. The first mask layer **12** may include an oxide layer (e.g., silicon oxide). For example, the first mask layer **12** may include thermally grown oxide, oxide deposited by chemical vapor deposition (CVD), and/or oxide deposited by atomic layer deposition (ALD). By way of example, the first mask layer **12** may have a thickness of between about 2 nm and about 30 nm, or a thickness of between about 5 nm and about 10 nm. In some embodiments, the second mask layer **14** includes silicon nitride, aluminum nitride, or other suitable materials. The second mask layer **14** may be deposited by CVD, plasma-enhanced CVD (PECVD), or other suitable deposition techniques. In some embodiments, the second mask layer **14** has a thickness of between about 1 nm and about 100 nm.

(15) An etching process is then applied to form a substrate alignment structure **20**. The substrate alignment structure **20** may include a plurality of trenches **22** within the substrate **10**. The etching process may include an anisotropic etching process such as reactive ion etching or ion beam etching. In some embodiments, each of the trenches **22** has a depth of about 50 nm to about 250 nm, or about 80 nm to about 100 nm. In some embodiments, the trenches **22** may have an aspect ratio about 10:1 to about 1:1, or for example, about 5:2. The second mask layer **14** may be removed after the substrate alignment structure **20** is formed.

(16) FIG. **5** illustrates a top view of the substrate alignment structure **20** in accordance with some embodiments. In some embodiments, the substrate alignment structure **20** includes regions **20A**, **20B**, **20C**, and **20D**. In some embodiments, the regions **20A** and **20C** of the substrate alignment structure **20** may have the same first pattern. In some embodiments, the regions **20B** and **20D** of the substrate alignment structure **20** may have the same second pattern. In some embodiments, 90 degree-rotated first pattern is similar to the second pattern. The substrate alignment structure **20** has a first width $W_{sub.1}$ and a second width $W_{sub.2}$. In some embodiments, the first width $W_{sub.1}$ equal the second width $W_{sub.2}$. In other embodiments, the first width $W_{sub.1}$ is different from the second width $W_{sub.2}$. In some embodiments, the first width $W_{sub.1}$ is between about 50 nm and about 1000 nm. In some embodiments, the second width $W_{sub.2}$ is between about 50 nm and about 1000 μ m. In some embodiments, a ratio $W_{sub.1}/W_{sub.2}$ is about 1. Registration and overlay errors may be reduced by aligning photomasks to the substrate alignment structure **20** in the subsequent lithography processes.

(17) In FIGS. **6A** and **6B**, appropriate wells may be formed in the substrate **10**. In some embodiments, a P-type well is formed in the N-type region **10N**, and an N-type well is formed in the P-type region **10P**. In other embodiments, a P-type well and an N-type well are formed in both N-type region **10N** and P-type region **10P**. In the embodiment with different types of wells, the different implant steps for the N-type region **10N** and P-type region **10P** may be achieved using a photoresist or other masks. For example, referring to FIGS. **6A** and **7A**, a first lithography step is

performed to pattern a P-type well in the N-type region **10N**. A second lithography step is performed to pattern an N-type well region in the P-type region **10P**. It will be understood that the first and second lithography steps may be performed in any order; for example, the N-type well in the P-type region **10P** may be implanted before the P-type well in the N-type region **10N**.

(18) Performing the first lithography step may include forming a photoresist layer over the substrate **10**, exposing the photoresist layer according to a pattern of a photomask, performing post-exposure bake processes, and developing the photoresist layer to form a patterned photoresist layer **30**. In some embodiments, as illustrated in FIGS. **6A** and **6B**, the patterned photoresist layer **30** has a first portion **30A** in the chip region **102** and a second portion **30B** in the dicing regions **103**. The second portion **30B** of the patterned photoresist layer **30** may be deposited over the trenches **22** and has protrusions that align to the trenches **22** and protrude over the substrate **10**. The second portion **30B** of the patterned photoresist layer **30** may be used to infer the exact position of the first portion **30A** of the patterned photoresist layer **30** (e.g., P-type implant mask) in the chip region **102**. For example, the position shift of the first portion **30A** of the patterned photoresist layer **30** in the chip region **102** may be inferred by measuring the overlay position shift between the second portion **30B** of the patterned photoresist layer **30** and the substrate alignment structure **20**.

(19) After the patterned photoresist layer **30** is formed, an ion implantation process is performed into the N-type region **10N** to form the P-type well, while the P-type region **10P** remains masked by the patterned photoresist layer **30**. By way of example, P-type impurities implanted via the ion implantation process into the P-type well may include boron, aluminum, gallium, indium, or other P-type acceptor material. After the ion implantation process, the patterned photoresist layer **30** may be removed, for example, by way of a solvent, resist stripper, ashing, or other suitable technique. The P-type impurities are implanted in the N-type region **10N** to a dose of equal to or less than 10^{15} cm.^{sup.}-2, such as between about 10^{12} cm.^{sup.}-2 and about 10^{15} cm.^{sup.}-2. In some embodiments, the P-type impurities may be implanted at an implantation energy of about 1 keV to about 10 keV.

(20) Thereafter, in some embodiments, the second lithography step is performed, where the second lithography step may include forming a photoresist layer over the substrate **10**, exposing the photoresist layer according to a pattern of a photomask, performing post-exposure bake processes, and developing the photoresist layer to form a patterned photoresist layer **32**. In some embodiments, as illustrated in FIGS. **7A** and **7B**, the patterned photoresist layer **32** has a first portion **32A** in the chip region **102** and a second portion **32B** in the dicing region **103**. The second portion **32B** of the patterned photoresist layer **32** may be deposited over the trenches **22** and has protrusions that align to the trenches **22** and protrude over the substrate **10**. The second portion **32B** of the patterned photoresist layer **32** may be used to infer the exact position of the first portion **32A** of the patterned photoresist layer **32** (e.g., N-type implant mask) in the chip region **102**. For example, the position shift of the first portion **32A** of the patterned photoresist layer **32** in the chip region **102** may be inferred by measuring the overlay position shift between the second portion **32B** of the patterned photoresist layer **32** and the substrate alignment structure **20**.

(21) After the patterned photoresist layer **32** is formed, an ion implantation process is performed into the P-type region **10P** to form the N-type well, while the N-type region **10N** remains masked by the patterned photoresist layer **32**. By way of example, N-type impurities implanted via the ion implantation process into the N-type well may include arsenic, phosphorous, antimony, or other N-type donor material. After the ion implantation process, the patterned photoresist layer **32** may be removed, for example, by way of a solvent, resist stripper, ashing, or other suitable technique. The N-type impurities may be implanted in the P-type region **10P** to a dose of equal to or less than 10^{15} cm.^{sup.}-2, such as between about 10^{12} cm.^{sup.}-2 and about 10^{15} cm.^{sup.}-2. In some embodiments, the N-type impurities may be implanted at an implantation energy of about 1 keV to about 10 keV.

(22) After performing the implantations of the N-type region **10N** and the P-type region **10P**, an

anneal process may be performed to activate the P-type and/or N-type impurities that were implanted. The anneal process may be performed in an atmosphere containing air or oxygen. The anneal process may be performed at a temperature of about 1000° C. to about 1250° C. for about 1 second to about 30 seconds. The first mask layer **12** is removed by a wet etching process after the implantation processes and before or after the anneal process, in accordance with some embodiments.

(23) Referring to FIGS. **8A** and **8B**, a multi-layer stack **40** that includes alternating layers of first semiconductor layers **42a**, **42b**, **42c** (collectively referred to as first semiconductor layer **42**) and second semiconductor layers **44a**, **44b** (collectively referred to as second semiconductor layer **44**) are formed over the substrate **10** and in the trenches **22** in accordance with some embodiments. In the FIGS. **8A** and **8B**, the multi-layer stack **40** is illustrated as including three layers of the first semiconductor layers **42a**, **42b**, **42c** and two layers of the second semiconductor layers **44a**, **44b** stacked alternately for illustrative purposes. The number of layers of the first semiconductor layer **42** and the second semiconductor layer **44** illustrated in FIGS. **8A** and **8B** are merely non-limiting examples. Other numbers of layers are also possible and are fully intended to be included within the scope of the present disclosure.

(24) Each layer of the multi-layer stack **40** may be epitaxially grown by rapid thermal chemical vapor deposition (RTCVD), metal-organic chemical vapor deposition (MOCVD), vapor phase epitaxy (VPE), molecular beam epitaxy (MBE), or other suitable methods. For example, in an embodiment that the first semiconductor layer **42a** is the bottom layer of the alternating layers, as illustrated in FIGS. **8A** and **8B**, the first semiconductor layer **42a** is epitaxially grown from the upper surface of the substrate **10** and in the trenches **22**; the second semiconductor layer **44a** is epitaxially grown over the upper surface of the first semiconductor layer **42a**; another first semiconductor layer **42b** is epitaxially grown over the upper surface of the second semiconductor layer **44a**; and other semiconductor layers are alternately epitaxially grown over the first semiconductor layer **42b**. In some embodiments, the first semiconductor layers **42a**, **42b**, **42c** and the second semiconductor layers **44a**, **44b** are conformally formed over the substrate **10** and in the trenches **22**, thereby having profiles substantially the same or similar to the profile of trenches **22** (i.e., substrate alignment structure **20**).

(25) In some embodiments, the first semiconductor layer **42** is formed of a first semiconductor material that has a different material from that of the substrate **10**. In some embodiments, the first semiconductor material further has a bandgap lower than about 1.1 eV. For example, the first semiconductor material may be silicon-germanium, where the germanium atomic concentration may be from about 20% to about 70%. In some embodiments, each of the first semiconductor layers **42a**, **42b**, **42c** has a thickness range of about 1 nm to about 50 nm. In some embodiments, the second semiconductor layer **44** is formed of a second semiconductor material different from that of the first semiconductor layer **42**. Also, the first semiconductor material and the second semiconductor material may be materials having a high-etch selectivity to one another. As such, the first semiconductor layer **42** of the first semiconductor material may be removed without significantly removing the second semiconductor layer **44** of the second semiconductor material, or vice versa, in the subsequent processes. In some embodiments, the second semiconductor layer **44** and the substrate **10** have the same material. In some embodiments, the second semiconductor layer **44** is formed of silicon, silicon carbon, or the like. Each of the second semiconductor layers **44a**, **44b** has a thickness of about 1 to about 50 nm in accordance with some embodiments.

(26) In FIGS. **9A** and **9B**, a third semiconductor layer **46** is formed over the multi-layer stack **40** in accordance with some embodiments. As illustrated in FIGS. **9B**, the multi-layer stack **40** may not completely fill the trenches **22**, and the trenches **22** may be filled by the third dielectric layer **46**. The third semiconductor layer **46** may be formed of the second semiconductor material and may be formed by the same methods of forming the second semiconductor material. In some embodiments, the third semiconductor layer **46** has a thickness that is thick enough to fill the trenches **22**

completely. For example, the third semiconductor layer **46** may have a thickness of about 1 to about 100 nm.

(27) Referring to FIGS. **10A** and **10B**, a planarization process is performed. In some embodiments, the planarization process includes a chemical mechanical polishing (CMP) process or any other suitable etching process. The planarization process removes the third semiconductor layer **46** outside the trenches **22** in accordance with some embodiments. For example, a portion of the third semiconductor layer **46** outside the trenches in the dicing region **103** and all the third semiconductor layer **46** in the chip region **102** are removed, exposing the multi-layer stack **40** and leaving a substantially flat upper surface of the third semiconductor layer **46** in the trenches **22**. As illustrated in FIGS. **10A** and **10B**, such flat upper surface of the third semiconductor layer **46** may be substantially level with the upper surface of the multi-layer stack **40** outside the trenches, such as the level with the upper surface of the first semiconductor layer **42c** outside the trenches **22**. In some embodiments, the first semiconductor layer **42c** may be used as a polishing stop layer in the embodiments illustrated in FIGS. **10A** and **10B**. In this context, the trenches **22** and the semiconductor layers **42**, **44**, **46** filled in and over the trenches **22** in the dicing region **103** are collectively referred to as an alignment structure **105**.

(28) It is noted that, in some embodiments, an anneal process is performed for rounding the bottom corners of the trenches **22** before the multi-layer stack **40** is formed. The anneal process may cause the trenches **1122** have rounded corners. The rounded corners may mitigate or avoid from stacking fault from occurring in the alternating layers of the multi-layer stack **40** or between the multi-layer stack **40** and the third semiconductor layer **46**. For example, FIG. **11** shows an alignment structure **1120** formed with the rounded trenches **1122**. The alignment structure **1105** may include semiconductor layers **42**, **44**, **46** formed with the rounded trenches **1122**. The anneal process for rounding the corners of the trenches **1122** is performed in an atmosphere containing H.sub.2 or a mixture of H.sub.2 and N.sub.2 in accordance with some embodiments. For example, the anneal process is performed under H.sub.2 or a mixture of H.sub.2 and N.sub.2. In some embodiments, the anneal process for rounding the corners of the trenches **1122** is performed at a temperature lower than that of the anneal process for activating the P-type/N-type impurities in P-type/N-type well. In some embodiments, the anneal process for rounding the corners of the trenches **1122** is performed at a temperature of about 700° C. to about 1,200° C. for about 1 second to about 600 seconds. FIG. **20** illustrates a structure resulting from such embodiments with the rounded trenches **1122**, for example.

(29) In FIGS. **12A** and **12B**, a patterned photoresist layer **48** is formed over the multi-layer stack **40** by one or more lithography steps. The lithography step may include forming a photoresist layer over the multi-layer stack **40** in the chip region **102** and the dicing region **103**, exposing the photoresist layer according to a pattern of a photomask, performing post-exposure bake processes, and developing the photoresist layer to form a patterned photoresist layer **48**. In some embodiments, as illustrated in FIGS. **12A** and **12B**, the patterned photoresist layer **48** has a first portion **48A** in the chip region **102** and a second portion **48B** in the dicing region **103**. The first portion **48A** of the patterned photoresist layer **48** is to define fins **50** and nanostructures **55A** in the chip region **102** in accordance with some embodiments. The second portion **48B** of the patterned photoresist layer **48** may be deposited over and align to the alignment structure **20'**. The second portion **48B** of the patterned photoresist layer **48** may be used to infer the exact position of the first portion **48A** of the patterned photoresist layer **48** (e.g., the mask to define the fins **50A** and nanostructures **55A**) in the chip region **102**. For example, the position shift of the first portion **48A** of the patterned photoresist layer **48** in the chip region **102** may be inferred by measuring the overlay position shift between the second portion **48B** of the patterned photoresist layer **48** and the alignment structure **20'**. Generally, the lithography process may also be applied in double-patterning or multi-patterning processes or in self-aligned processes. In some embodiments that the measured overlay position shift of the patterned photoresist layer **48** is larger than a predetermined

value or the process window, the patterned photoresist layer **48** may be removed, and the steps of forming the patterned photoresist layer **48** may be performed again.

(30) In some embodiments, because the first semiconductor layer **42** and the second semiconductor layer **44** are conformally formed over the substrate **10** and along the trenches **22**, the profile of the trenches **22** can be measured by detecting the profile of the first semiconductor layer **42** or the second semiconductor layer **44**, thereby the accuracy of profile measurement of the positions of the alignment structures **20'** (e.g., the trenches) may be improved as compared to an alignment structure that has a thick layer of semiconductor material (e.g., a silicon layer or silicon oxide) filling in the trenches **22**. The thick layer filled in the trenches **22** would interfere with the measurement accuracy and sensitivity of the profile of the trenches **22** because the detecting light used to measure the profile of the trenches **22** would be absorbed by the thick layer, especially when the thick layer and the substrate are formed of similar materials. In some embodiments, forming one or more thin layers (e.g., the first semiconductor layer **42**) having a material different from the substrate **10** can mitigate or avoid this problem. For example, in an embodiment that the first semiconductor layer **42a** is formed of silicon-germanium and the second and third semiconductor layers **44a**, **44b**, **46** are formed of silicon, substantially all of the detecting light may penetrate the second and third semiconductor layers **44** and **46** to reach the bottommost layer of the multi-layer stack **40**, the first semiconductor layer **42a**. Because the first semiconductor layer **42** has a bandgap lower than 1.1 eV, the first semiconductor layer **42** may be detected by a light having a wavelength over about 1.1 μm , without being absorbed by the thin silicon layers (e.g., second and third semiconductor layers **44a**, **44b**, **46**) which may be used as channel layers of the nano-FETs. Thus, with the formation of alignment structures **20'**, accurate profiles of the trenches **22** and accurate overlay position shift between the alignment structures **20'** and photoresist patterns that are used to define fins **50** and nanostructures **55** can be measured.

(31) In some embodiments, the first semiconductor layers **42** or the second semiconductor layers **44** may serve as the channel layers of nanostructures in the chip region **102**. Thus, the alignment structure **20'** may be formed without adding additional layers and may be easily integrated into any semiconductor devices and processes of manufacturing them. In further embodiments, with the formation of the third semiconductor layer **46**, the second portion **48B** of the patterned photoresist layer **48** may stand on a flat upper surface, which may reduce the possibility of pattern deformation because depositing on an uneven surface.

(32) In FIGS. **13A** and **13B**, the fins **50A** and nanostructures **55A** in the chip region **102** and the fins **50B** and nanostructures **55B** in the dicing region **103** are formed by a patterning process in accordance with some embodiments. The fins **50A**, **50B** and nanostructures **55A**, **55B** may be formed by etching the substrate **10** according to the patterns of the first portion **48A** and the second portion **48B** of the patterned photoresist layer **48**. In FIG. **13A**, each of the fins **50A** have a substantially flat upper surface, and respective nanostructures **55A** including the first and second semiconductor layers **42**, **44** are disposed over the flat upper surface of the fins **50A**, in accordance with some embodiments. The fins **50A** may be formed from the substrate **10** and have the same material as the substrate **10**. It is noted that, in FIG. **13A**, the fins **50A** and nanostructures **55A** having substantially equal widths are for illustrative purposes. In some embodiments, widths of the fins **50A** in the N-type region **10N** may be greater or thinner than the fins **50A** in the P-type region **10P**. Further, while each of the fins **50A** and the nanostructures **55A** are illustrated as having a consistent width throughout, in other embodiments, the fins **50A** and/or the nanostructures **55A** may have tapered sidewalls such that a width of each of the fins **50A** and/or the nanostructures **55A** continuously increases in a direction towards the substrate **10**. In such embodiments, fins **50A** and respective nanostructures **55A** over the fins **50A** may have a different width and be trapezoidal in shape.

(33) In FIG. **13B**, the trenches **22** are disposed over corresponding ones of the fins **50B** in accordance with some embodiments. Each of the fins **50B** may have an upper surface that is equal

to the profile of the trenches **22**. For example, each of the fins **50B** may have a concave upper surface **50S**. The concave upper surface **50S** may have the depth d of about 50 nm to about 250 nm, or about 80 nm to about 100 nm. In some embodiments, because the semiconductor layers **42**, **44** and **46** are formed in the trenches **22**, the first semiconductor layer **42**, the second semiconductor layer **44**, and the bottom surface of the nanostructures **55B** are conformal to the concave upper surface **50S** of the fins **50B**. The fins **50B** may be formed from the substrate **10** and have the same material as the substrate **10**. In some embodiments, the patterned photoresist layer **48** may be removed, for example, by way of a solvent, resist stripper, ashing, or other suitable technique. In the context, the nanostructures **55B** and the fins **50B** are collectively referred to as the alignment structure **105**.

(34) In FIGS. **14A** and **14B**, an insulation layer **60** is deposited over the substrate **10**, the fins **50A**, **50B** and the nanostructures **55A**, **55B**. The insulation layer **60** may be an oxide, such as silicon oxide, a nitride, the like, or a combination thereof, and may be formed by high-density plasma CVD (HDP-CVD), flowable CVD (FCVD), the like, or a combination thereof. Other insulation materials formed by any acceptable process may be used. In the illustrated embodiment, the insulation material is silicon oxide formed by an FCVD process. An anneal process may be performed once the insulation layer **60** is formed. Although the insulation material is illustrated as a single layer, some embodiments may utilize multiple layers. For example, in some embodiments, a liner (not separately illustrated) may first be formed along a surface of the substrate **10**, the fins **50A** and **50B**, and the nanostructures **55A** and **55B**. Thereafter, a fill material, such as those discussed above, may be formed over the liner.

(35) In FIGS. **15A** and **15B**, a removal process is applied to the insulation layer **60** in the chip region **102** to form isolation features **62** adjacent the fins **50A**. In some embodiments, the isolation features **62** are shallow trench isolation (STI) features. The removal process includes removing excess insulation layer **60** over and adjacent the nanostructures **55A** in the chip region **102** while not removing the insulation layer **60** over and adjacent the nanostructures **55B** in the dicing region **103** in accordance with some embodiments. In some embodiments, the removal process may be an etch-back process or a combination of the etch-back process and a CMP process. In some embodiments, a photoresist layer may be applied over the dicing region **103**, while exposing the chip region **102** before the removal process is performed.

(36) In FIGS. **16A** and **16B**, a dummy dielectric layer **70** is formed over the fins **50A** and/or the nanostructures **55A** in the chip region **102**. The dummy dielectric layer **70** may be, for example, silicon oxide, silicon nitride, a combination thereof, or the like, and may be deposited or thermally grown according to acceptable techniques. A dummy gate layer **72** is formed over the dummy dielectric layer **70**. The dummy gate layer **72** may be deposited over the dummy dielectric layer **70** and then planarized, such as by a CMP. The dummy gate layer **72** may be a conductive or non-conductive material and may be selected from a group including amorphous silicon, polycrystalline-silicon (polysilicon), polycrystalline silicon-germanium (poly-SiGe), metallic nitrides, metallic silicides, metallic oxides, and metals. The dummy gate layer **72** may be deposited by physical vapor deposition (PVD), CVD, sputter deposition, or other techniques for depositing the selected material. The dummy gate layer **72** may be made of other materials that have a high etching selectivity from the etching the isolation features **62**. It is noted that the dummy dielectric layer **70** is shown covering only the fins **50A** and the nanostructures **55A** for illustrative purposes only. In some embodiments, the dummy dielectric layer **70** may be deposited such that the dummy dielectric layer **70** covers the isolation features **62**, such that the dummy dielectric layer **70** extends between the dummy gate layer **72** and the isolation features **62**.

(37) Referring to FIG. **17**, source/drain features **80** are then formed on opposite sides of the nanostructures **55A**. In some embodiments, the source/drain features **80** are formed by epitaxially growing a semiconductor material layer from the substrate **10** on opposite sides of the nanostructures **55A**. In some embodiments, portions of the fins **50A** and nanostructures **55A** that

are not covered by the dummy gate layer **72** are etched to create recesses between the isolation features **62**. In some embodiments, the source/drain features **80** are epitaxially grown in the recesses and over the isolation features **62**, as illustrated in FIG. **17**. In some examples, dummy sidewall spacers (not shown in Figures) may be formed prior to epitaxial source/drain growth and removed after epitaxial source/drain growth. Additionally, in some embodiments, the main sidewall spacers **82** may be formed, as described above, after epitaxial source/drain growth. In some embodiments, the source/drain features **80** may be formed in P-type region **10P** to provide a PMOSFET, and the source/drain features **80** include materials exerting a tensile strain in the channel regions, such as silicon, SiC, SiCP, SiP, or the like. In some embodiments, the source/drain features **80** may be formed in the N-type region **10N** to provide a NMOSFET, and the source/drain features **80** include materials exerting a compressive strain in the channel regions, such as SiGe, SiGeB, Ge, GeSn, or the like. The source/drain features **80** may have surfaces raised from respective surfaces of the fins and may have facets. In some embodiments, after the formation of the source/drain features **80**, an anneal process may be performed to activate the impurities in the source/drain features **80**. As illustrated in FIG. **17**, source/drain features **80** are separated from each other in accordance with some embodiments. In other embodiments, some of the source/drain features **80** may be merged or physically connected to each other.

(38) In FIGS. **18A** and **18B**, the dummy gate layer **72** are removed in one or more etching steps so that recesses **85** are formed in the chip region **102**. Portions of the dummy dielectric layer **70** in the recesses **85** are also removed. In some embodiments, the dummy gate layer **72** and the dummy dielectric layer **70** are removed by an anisotropic dry etch process. For example, the etching process may include a dry etch process using reaction gas(es) such as reactive ion etching. Each recess **85** exposes and/or overlies the nanostructures **55A** in the chip region **102**. During the removal, the dummy dielectric layer **70** may be used as etch stop layer when the dummy gate layer **72** are etched. The dummy dielectric layer **70** may then be removed after the removal of the dummy gate layer **72**.

(39) In FIGS. **18A** and **18B**, the first semiconductor layer **42** in the chip region **102** may be removed, and the second semiconductor layer **44** in the chip region **102** may remain and will act as channel regions of nano-FETs in both N-type region **10N** and P-type region **10P**. In such embodiments, the channel regions in both N-type region **10N** and P-type region **10P** may have the same material composition (e.g., silicon or another semiconductor material).

Tetramethylammonium hydroxide (TMAH), ammonium hydroxide (NH₄OH), or the like may be used to remove the first semiconductor layer **42**.

(40) In other embodiments, the second semiconductor layer **44** in the N-type region **10N** and the P-type region **10P** will be removed (not shown in Figures). Also, the first semiconductor layer **42** in the N-type region **10N** and the P-type region **10P** will act as channel regions of nano-FETs in both P-type region **10P** and N-type region.

(41) In FIGS. **19A** and **19B**, gate dielectric layers **90** and gate electrodes **92** are formed for replacement gates. The gate dielectric layers **90** is deposited conformally in the recesses **85**. In the illustrated example, the gate dielectric layers **90** may be formed on top surfaces and sidewalls of the fins **50A** and on top surfaces, sidewalls, and bottom surfaces of nanostructures **55A**, for example, on the top surfaces, sidewalls, and bottom surfaces of second semiconductor layer **44**.

(42) In accordance with some embodiments, the gate dielectric layers **90** includes one or more dielectric layers, such as an oxide, a metal oxide, the like, or combinations thereof. For example, in some embodiments, the gate dielectric layers **90** may include a silicon oxide layer and a metal oxide layer over the silicon oxide layer. In some embodiments, the gate dielectric layers **90** includes a high-k dielectric material, and in these embodiments, the gate dielectric layers **90** may have a k value greater than about 7.0, and may include a metal oxide or a silicate of hafnium, aluminum, zirconium, lanthanum, manganese, barium, titanium, lead, and combinations thereof. The formation methods of the gate dielectric layers **90** may include molecular-beam deposition

(MBD), ALD, PECVD, and the like.

(43) The formation of the gate dielectric layers **90** in the N-type region **10N** and the P-type region **10P** may occur simultaneously such that the gate dielectric layers **90** in N-type region **10N** and the P-type region **10P** are formed from the same materials, and the formation of the gate electrodes **92** may occur simultaneously such that the gate electrodes **92** in the N-type region **10N** and the P-type region **10P** are formed from the same materials. In some embodiments, the gate dielectric layers **90** in the N-type region **10N** and the P-type region **10P** may be formed by distinct processes, such that the gate dielectric layers **90** may have different materials and/or have a different number of sub-layers, and/or the gate electrodes **92** in the N-type region **10N** and the P-type region **10P** may be formed by distinct processes, such that the gate electrodes **92** may have different materials and/or have a different number of sub-layers in the N-type region **10N** and the P-type region **10P**. Various masking steps may be used to mask and expose appropriate regions when using distinct processes.

(44) After the filling of the recesses **85**, a planarization process, such as a CMP, may be performed to remove the excess portions of the gate dielectric layers **90** and the gate electrodes **92**. The remaining portions the gate electrodes **92** and the gate dielectric layers **90** thus form replacement gate structures of the resulting nano-FETs. The gate electrodes **92** and the gate dielectric layers **90** may be collectively referred to as “gate structures.”

(45) FIG. **20** illustrates a cross-sectional view according to the section C-C' of the nano-FETs illustrated in FIG. **2**, in accordance with some alternative embodiments. In FIGS. **20**, like reference numerals indicate like elements formed by like processes as the structure of FIGS. **3A** through **19B**. For example, the nano-FETs in these embodiments may have an alignment structure **1105**, and each of the alignment structures **1105** may comprise nanostructures **1155B** disposed over a fin **1150B**. The nanostructures **1155B** are similar to the nanostructures **55B** as those discussed above, and the fin **1150B** is similar to the fin **50B** as those discussed above, where the fin **1150B** has a rounded concave upper surface **1150S**. The nanostructures **1155B** has a bottom surface conformal to the rounded concave upper surface **1150S**. The rounded concave upper surface **1150B** may mitigate or avoid from stacking fault from occurring in the alternating layers in the nanostructure **1155B**.

(46) In an embodiment, a method of a semiconductor device fabrication includes: providing a substrate having a first region and a second region; forming a plurality of trenches in the first region of the substrate; forming a multi-layer stack over the substrate and in the trenches; and patterning the multi-layer stack and the substrate to form first nanostructures over first fins in the first region and second nanostructures over second fins in the second region, where the multi-layer stack includes at least one of first semiconductor layers and at least one of second semiconductor layer stacked alternately, and the plurality of trenches are in corresponding ones of the first fins.

(47) In another embodiment, a method for a semiconductor device fabrication includes forming a plurality of trenches in a first region of a substrate; annealing the substrate in H.sub.2 or a mixture of H.sub.2 and N.sub.2; after annealing, epitaxially growing alternating first semiconductor layers and second semiconductor layers over the substrate in the first region and a second region, the alternating first semiconductor layers and second semiconductor layers being extending into the trenches; patterning the alternating first semiconductor layers and second semiconductor layers to form nanostructures in the first region and in the second region; and forming gate structures over respective portions of the nanostructures in the second region.

(48) In yet embodiment, a semiconductor device includes a substrate having a dicing region and a chip region; a gate structure disposed in the chip region; and an alignment structure disposed in the dicing region. The alignment structure includes fins protruding from the substrate and nanostructures disposed over the fins, where each of the nanostructures comprise alternately stacked first semiconductor layers and second semiconductor layers.

(49) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other

processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method of semiconductor device fabrication, the method comprising: forming a plurality of trenches in a first region of a substrate; forming a multi-layer stack over the first region and a second region of the substrate, wherein the multi-layer stack extends into the trenches, wherein the multi-layer stack comprises at least one first semiconductor layer and at least one second semiconductor layer stacked alternately; and patterning the multi-layer stack and the substrate to form first nanostructures over first fins in the first region and second nanostructures over second fins in the second region, wherein the plurality of trenches in corresponding ones of the first fins.
2. The method of claim 1, further comprising forming: forming an insulating layer over the first nanostructures and the second nanostructures; and etching the insulating layer in the second region without etching the insulating layer in the first region.
3. The method of claim 2, wherein the step of etching the insulating layer exposes the second nanostructures in the second region, and the method further comprises forming respective gate structures over the insulating layer and across the second nanostructures.
4. The method of claim 3, further comprising removing the first semiconductor layer in the second region without removing the first semiconductor layer in the first region before forming the gate structures.
5. The method of claim 1, wherein the at least one second semiconductor layer and the substrate are a same material.
6. The method of claim 1, wherein the first region is a dicing region.
7. The method of claim 1, wherein each of the plurality of trenches have a depth in a range from 50 nm to 250 nm.
8. The method of claim 1, further comprising: forming a third semiconductor layer over the multi-layer stack in the first region and in the second region, wherein the third semiconductor layer extends into the plurality of trenches; and performing a polishing process, wherein after the polishing process an upper surface of the third semiconductor layer in the first region is level with an upper surface of the multi-layer stack.
9. The method of claim 8, wherein the polishing process comprises completely removing the third semiconductor layer in the second region.
10. The method of claim 8, wherein the polishing process comprises using the first semiconductor layer or the second semiconductor layer as a polishing stop layer.
11. The method of claim 1, further comprising rounding corners of the plurality of trenches before forming the multi-layer stack.
12. The method of claim 11, wherein the rounding comprises performing an anneal process to the substrate before forming the multi-layer stack in H.sub.2 or a mixture of H.sub.2 and N.sub.2.
13. A method of semiconductor device fabrication, the method comprising: annealing a substrate in an atmosphere containing oxygen; forming a plurality of trenches in a first region of a substrate, after annealing the substrate; annealing the substrate in H.sub.2 or a mixture of H.sub.2 and N.sub.2, wherein the step of annealing the substrate in H.sub.2 or a mixture of H.sub.2 and N.sub.2 is operated at a temperature lower than that of the step of annealing the substrate in an atmosphere containing oxygen; after annealing, epitaxially growing alternating first semiconductor layers and second semiconductor layers over the substrate in the first region and a second region, wherein the alternating first semiconductor layers and second semiconductor layers extend into the trenches;

patterning the alternating first semiconductor layers and second semiconductor layers to form nanostructures in the first region and in the second region; and forming gate structures over respective portions of the nanostructures in the second region.

14. The method of claim 13, wherein the step of annealing the substrate in an atmosphere containing oxygen is performed at a temperature in a range of from 1000° C. to 1250° C.

15. The method of claim 14, wherein the step of annealing the substrate in H.sub.2 or a mixture of H.sub.2 and N.sub.2 is performed at a temperature in a range of from 700° C. to 1,200° C.

16. A method of semiconductor device fabrication, the method comprising: forming an alignment trench in an alignment region of a semiconductor wafer; depositing over the semiconductor wafer a stack of alternating first semiconductor layers and second semiconductor layers, the stack extending over the semiconductor wafer in a device region of the semiconductor wafer and in the alignment region of the semiconductor wafer, the stack further lining the alignment trench in the alignment region of the semiconductor wafer to form a first alignment structure; patterning the stack and the semiconductor wafer to form a channel stack over a first fin in the device region of the semiconductor wafer and to form a second alignment structure over a second fin in the alignment region of the semiconductor wafer, wherein the second alignment structure includes portions of the first semiconductor layers and the second semiconductor layers extending below a topmost surface of the second fin; depositing an insulation layer over the channel stack and first fin and over the second alignment structure; and forming a gate over the channel stack.

17. The method of claim 16, further comprising: depositing a photoresist layer over the stack of alternating first semiconductor layers and second semiconductor layers in the device region and over the first alignment structure in the alignment region; patterning the photoresist layer to form a first patterning structure in the device region of the semiconductor wafer and a second patterning structure over the first alignment structure in the alignment region; and determining an amount of position shift for the first patterning structure by measuring an amount of overlay position shift of the second patterning structure relative to the first alignment structure.

18. The method of claim 16, wherein the step of forming the alignment trench in the alignment region of the semiconductor wafer includes forming a pattern of trenches, the pattern including first trenches extending in a first longitudinal direction and second trenches extending orthogonal to the first trenches.

19. The method of claim 16, further comprising: filling the alignment trench with a dielectric fill material after lining the alignment trench with the stack.

20. The method of claim 16, further comprising rounding corners of the alignment trench after the step of depositing over the semiconductor wafer the stack of alternating the first semiconductor layers and the second semiconductor layers.
