

# US Patent & Trademark Office

## Patent Public Search | Text View

---

United States Patent Application Publication

20250287587

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

YANG; Chih-Kai

---

## MEMORY DEVICE AND MANUFACTURING METHOD THEREOF

---

### Abstract

A memory device includes an array region, a staircase region, a reference structure in the array region and the staircase region, a stacked structure in the array region and the staircase region, and a wall structure extending along a direction from the array region to the staircase region. The reference structure includes a conductive structure and a dielectric structure embedded within the conductive structure in the staircase region. The dielectric structure includes a first dielectric layer and a second dielectric layer disposed on a top surface, a sidewall and a bottom surface of the first dielectric layer. The sidewall of the first dielectric layer is connected to the top surface and the bottom surface of the first dielectric layer. The stacked structure includes conductive layers and insulating layers alternately stacked over the reference structure. The wall structure penetrates the stacked structure and beyond the dielectric structure.

---

**Inventors:** YANG; Chih-Kai (Kaohsiung City, TW)

**Applicant:** MACRONIX INTERNATIONAL CO., LTD. (HSINCHU, TW)

**Family ID:** 1000007796550

**Appl. No.:** 18/598047

**Filed:** March 07, 2024

---

### Publication Classification

**Int. Cl.:** H10B43/27 (20230101); H01L23/60 (20060101)

**U.S. Cl.:**

**CPC** H10B43/27 (20230201); H01L23/60 (20130101);

---

### Background/Summary

## BACKGROUND

### Technical Field

[0001] The present disclosure relates to a memory device and a manufacturing method of the memory device.

### Description of Related Art

[0002] In semiconductor industry, the structures of memory devices have been changed constantly, and the storage capacity of the memory devices has been increased continuously. Memory devices are used in storage elements for many products such as MP3 players, digital cameras, computer files, and so on. As the application increases, the demand for the memory devices focuses on small size and large memory capacity. For satisfying the requirement, a memory device having a high element density, a small size and a solid structure are in need. Therefore, it is important to provide robust processes in the manufacture of the memory devices.

### SUMMARY

[0003] One aspect of the present disclosure is a memory device.

[0004] According to some embodiments of the present disclosure, a memory device includes an array region, a staircase region, a reference structure, a stacked structure and a wall structure. The reference structure is disposed in the array region and the staircase region, and the reference structure includes a conductive structure and a dielectric structure embedded within the conductive structure in the staircase region. The dielectric structure includes a first dielectric layer and a second dielectric layer disposed on a top surface of the first dielectric layer, a sidewall of the first dielectric layer and a bottom surface of the first dielectric layer, in which the sidewall of the first dielectric layer is connected to the top surface of the first dielectric layer and the bottom surface of the first dielectric layer. The stacked structure includes a plurality of conductive layers and a plurality of insulating layers alternately stacked over the reference structure, and the stacked structure is disposed in the array region and the staircase region. The wall structure extends along a direction from the array region to the staircase region, and the wall structure penetrates the stacked structure and beyond the dielectric structure.

[0005] In some embodiments of the present disclosure, the conductive structure includes a first conductive layer and a second conductive layer. The first conductive layer is disposed under the dielectric structure. The second conductive layer is disposed over the first conductive layer, and the second conductive layer includes a first portion along a top surface of the dielectric structure and a second portion along a sidewall of the dielectric structure in the staircase region.

[0006] In some embodiments of the present disclosure, a bottommost surface of the second dielectric layer of the dielectric structure is disposed below a topmost surface of the first conductive layer.

[0007] In some embodiments of the present disclosure, the memory devices further includes a discharge electrode extending downwards from a bottom surface of the first conductive layer and in electrical contact with the reference structure.

[0008] In some embodiments of the present disclosure, the second dielectric layer of the dielectric structure is in contact with a sidewall of the second portion of the second conductive layer.

[0009] In some embodiments of the present disclosure, a portion of the second dielectric layer of the dielectric structure extends to a bottom surface of the second portion of the second conductive layer.

[0010] In some embodiments of the present disclosure, the memory device further includes a substrate over the stacked structure.

[0011] In some embodiments of the present disclosure, the wall structure is in electrical contact with the reference structure.

[0012] In some embodiments of the present disclosure, the memory device further includes a discharge electrode extending downwards from a bottom surface of the reference structure and in

electrical contact with the reference structure in a discharge region.

[0013] In some embodiments of the present disclosure, the conductive structure includes a first conductive layer and a second conductive layer. The second conductive layer is disposed over the first conductive layer. A ratio of a thickness of the second conductive layer to a width of the discharge electrode is larger than 2.

[0014] In some embodiments of the present disclosure, the first dielectric layer and the second dielectric layer include different materials.

[0015] Another aspect of the present disclosure is a memory device.

[0016] According to some embodiments of the present disclosure, a memory device includes a reference structure, a stacked structure and a wall structure. The reference structure includes a conductive structure and a dielectric structure embedded within the conductive structure. The dielectric structure includes a first dielectric layer and a second dielectric layer. The second dielectric layer has an extension portion extending downward from a bottom surface of the second dielectric layer. The stacked structure including a plurality of conductive layers and a plurality of insulating layers alternately stacked over the reference structure. The wall structure penetrates the stacked structure and beyond the dielectric structure.

[0017] In some embodiments of the present disclosure, the second dielectric layer of the dielectric structure covers a top surface of the first dielectric layer, a sidewall of the first dielectric layer and a bottom surface of the first dielectric layer.

[0018] In some embodiments of the present disclosure, the extension portion of the second dielectric layer of the dielectric structure has an L-shaped cross-section.

[0019] In some embodiments of the present disclosure, the conductive structure includes a first conductive layer and a second conductive layer over the first conductive layer. The dielectric structure is disposed between the first conductive layer and the second conductive layer.

[0020] In some embodiments of the present disclosure, the memory device further includes a discharge electrode extending downwards from the first conductive layer and in electrical contact with the reference structure.

[0021] In some embodiments of the present disclosure, a bottommost surface of the extension portion of the second dielectric layer of the dielectric structure is below a topmost surface of the first conductive layer.

[0022] In some embodiments of the present disclosure, the memory device further includes a discharge electrode extending downwards from the reference structure and in electrical contact with the reference structure.

[0023] In some embodiments of the present disclosure, the wall structure includes a conductive material with an insulating material on sidewalls.

[0024] Another aspect of the present disclosure is a manufacturing method of a memory device.

[0025] According to some other embodiments of the present disclosure, the manufacturing method of a memory device includes forming a first conductive layer and a dielectric stack in an array region and a staircase region of the memory device. An opening is formed in a first portion of the dielectric stack in the staircase region. A dielectric material is deposited over the dielectric stack and lining the opening. A second conductive layer is formed over the dielectric material and filling the opening. Insulating layers and sacrificial material layers are formed alternately stacked over the second conductive layer. A memory structure is formed through the insulating layers, the sacrificial material layers, the second conductive layer, the dielectric stack and the first conductive layer in the array region. A slit trench is formed through the insulating layers, the sacrificial material layers and the second conductive layer in the array region and the staircase region, in which the slit trench exposes a sidewall of the second conductive layer and a sidewall of the dielectric material in the staircase region. An etching process is performed to remove a second portion of the dielectric stack in the array region to expose the memory structure, in which the first portion of the dielectric stack in the staircase region remains after the etching process is complete. A bottom electrode layer is

formed in electrical contact with the memory structure. The sacrificial material layers are replaced with conductive layers.

---

## Description

### BRIEF DESCRIPTION OF THE DRAWINGS

[0026] The disclosure can be more fully understood by reading the following detailed description of the embodiments, with reference made to the accompanying drawings as follows:

[0027] FIGS. **1A**, **2A**, **3A**, **4A**, **5A**, **6A**, **7A**, **8A**, **9A**, **10A**, **11A**, **12A**, **13A**, **14A**, **15A** and **16A** are top views of a process at various stages of a manufacturing method of a memory device according to some embodiments of the present disclosure.

[0028] FIGS. **1B**, **2B**, **3B**, **4B**, **5B**, **6B**, **7B**, **8B**, **9B**, **10B**, **11B**, **12B**, **13B**, **14B**, **15B** and **16B** are cross-sectional views of a process at various stages of a manufacturing method of a memory device according to some embodiments of the present disclosure.

[0029] FIG. **12C** is a cross-sectional view taking along line **X1-X1'** of FIG. **12A**.

[0030] FIG. **17** is a top view of a discharge electrode according to some embodiments of the present disclosure.

[0031] FIG. **18** is a top view of a discharge electrode according to some embodiments of the present disclosure.

[0032] FIG. **19** is a partially cross-sectional view of a discharge electrode in a discharge region according to some embodiments of the present disclosure.

[0033] FIG. **20** is a top view of the discharge electrode of FIG. **19** according to some embodiments of the present disclosure.

[0034] FIG. **21** is a top view of the discharge electrode of FIG. **19** according to some embodiments of the present disclosure.

[0035] FIG. **22** is a cross-sectional view of the memory device including metal layers and a passivation layer according to some embodiments of the present disclosure.

[0036] FIG. **23** is a cross-sectional view of the memory device including metal layers and a passivation layer according to some embodiments of the present disclosure.

### DETAILED DESCRIPTION

[0037] Reference will now be made in detail to the present embodiments of the disclosure, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers are used in the drawings and the description to refer to the same or like parts.

[0038] As used herein, “around”, “about”, “approximately”, or “substantially” shall generally mean within 10 percent, or within 5 percent of a given value or range. Numerical quantities given herein are approximated, meaning that the term “around”, “about”, “approximately”, or “substantially” can be inferred if not expressly stated.

[0039] In the embodiments of the present disclosure, a memory device and a manufacturing method of the same are provided. The memory device **100** includes an array region **AR**, a staircase region **SR** and a discharge region **DR**. The array region **AR** is a region to form a memory array. The staircase region **SR** is adjacent to the array region **AR**. The discharge region **DR** may be disposed in a region of the array region **AR** without forming a memory structure and/or a wall structure described in more detail below or a region of the staircase region without forming a support pillar structure described in more detail below. The discharge region **DR** may be disposed in four edges of a semiconductor die, scribe lines, and so on. It is noted that the term “top view” may be used herein for ease of description to refer to as a cross-sectional view of a dielectric layer **150** (i.e., the cross-section along line **A-A'** in FIG. **1B**) of the memory device **100** in order to highlight the technical features of the inventive concept. Further, FIGS. **1A**, **2A**, **3A**, **4A**, **5A**, **6A**, **7A**, **8A**, **9A**, **10A**, **11A**, **12A**, **13A**, **14A**, **15A**, and **16A** are top views of layouts of the memory device **100**

according to some embodiments of the present disclosure, and some elements are not illustrated in those top views for simplicity. FIGS. 1A-1B, 2A-2B, 3A-3B, 4A-4B, 5A-5B, 6A-6B, 7A-7B, 8A-8B, 9A-9B, 10A-10B, 11A-11B, 12A-12C, 13A-13B, 14A-14B, 15A-15B, and 16A-16B are views of a process at various stages of a manufacturing method of a memory device **100** according to some embodiments of the present disclosure.

[0040] FIG. 1A is a top view of a step of manufacturing the memory device **100**, and FIG. 1B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 1A. Referring to FIGS. 1A and 1B, a substrate **110** is provided. The substrate **110** extends along a plane defined by a first direction X (or referred as X axis) and a second direction Y (or referred as Y axis), in which the first direction X is perpendicular to the second direction Y. An insulating layer **120** is formed on the substrate **110**. Then, a first conductive layer **130** and a dielectric stack DS are formed over the substrate **110** in the array region AR, the staircase region SR, and the discharge region DR. The insulating layer **120** is in contact with the substrate **110**. The first conductive layer **130** is formed over and in contact with the insulating layer **120**. The dielectric stack DS is formed over and in contact with the first conductive layer **130**.

[0041] In some embodiments, forming the dielectric stack DS includes forming a dielectric layer **140a**, a dielectric layer **150**, and a dielectric layer **160** in sequence. The dielectric layer **140a** is in contact with the first conductive layer **130**, the dielectric layer **150** is in contact with the dielectric layer **140a**, and the dielectric layer **160** in contact with the dielectric layer **150**. In some embodiments, the dielectric layer **140a** is separated from the dielectric layer **160** by the dielectric layer **150**. In some embodiments, the dielectric layer **140a** and the dielectric layer **150** include different materials, and the dielectric layer **140a** and the dielectric layer **160** include the same material. For example, the dielectric layer **140a** includes oxide (e.g., silicon oxide), the dielectric layer **150** includes nitride (e.g., silicon nitride), and the dielectric layer **160** includes oxide (e.g., silicon oxide).

[0042] After forming the dielectric stack DS over the substrate **110**, an opening O1 is formed in a first portion DS1 of the dielectric stack DS in the staircase region SR. In greater details, the opening O1 downwards penetrates through the dielectric stack DS and exposes the first conductive layer **130**. In some embodiments, forming the opening O1 further includes etching a portion of the first conductive layer **130** such that an etched surface **133** of the first conductive layer **130** is below a top surface **131** of the first conductive layer **130** (or a bottommost surface of the dielectric stack DS). In some embodiments, a patterned photoresist is formed on the dielectric layer **160** of the dielectric stack DS, in which the patterned photoresist may be formed by suitable deposition, development and/or etching techniques. Then, the dielectric stack DS not covered by the patterned photoresist is etched by using the patterned photoresist as an etching mask to form the opening O1. After the opening O1 are formed, the patterned photoresist may be removed by using a photoresist stripping process (e.g., ashing process).

[0043] As shown in FIG. 1A, the opening O1 is disposed in the staircase region SR and spaced apart from the array region AR. The opening O1 may include first portions O1a and a second portion O1b substantially perpendicular to the first portions O1a. Specifically, the first portions O1a extend along the first direction X and the second portion O1b extends along the second direction Y. The first portions O1a are connected to the second portion O1b. In some embodiments, the opening O1 has a comb shape top profile.

[0044] In some embodiments, the substrate **110** is a semiconductor substrate, such as a silicon substrate, a silicon germanium substrate, a silicon carbide substrate, or the like. The substrate **110** may include interconnect structures having conductive contacts, transistors, or other similar components. In some embodiments, the insulating layer **120** and the dielectric layer **140a** include the same material. For example, the insulating layer **120** and the dielectric layer **140a** includes oxide (e.g., silicon oxide). In some embodiments, the first conductive layer **130** includes

semiconductor materials (e.g., polysilicon).

[0045] FIG. 2A is a top view of a step of manufacturing the memory device **100**, and FIG. 2B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 2A. Referring to FIGS. 1A-1B and 2A-2B, after forming the opening O1, an etching process is performed to remove the dielectric layer **160** of the dielectric stack DS such that a top surface **151** of the dielectric layer **150** of the dielectric stack DS is exposed. In some embodiments, the etching process of removing the dielectric layer **160** is a dry etching process, a wet etching process, or a combination thereof.

[0046] FIG. 3A is a top view of a step of manufacturing the memory device **100**, and FIG. 3B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 3A. Referring to FIGS. 3A and 3B, a dielectric material **140b** is deposited over the dielectric stack DS and lining the opening O1. In some embodiments, the dielectric material **140b** covers the top surface **151** of the dielectric layer **150** of the dielectric stack DS. The dielectric material **140b** is in contact with the first conductive layer **130** and a sidewall of the dielectric stack DS. In some embodiments, a bottommost surface **143** of the dielectric material **140b** is below a topmost surface **131** of the first conductive layer **130**. In some embodiments, a thickness T1 of the dielectric material **140b** is greater than or equal to a thickness T2 of the dielectric layer **140a** of the dielectric stack structure DS. In some embodiments, a ratio of the thickness T1 of the dielectric material **140b** to the thickness T2 of the dielectric layer **140a** is in a range from 1 to 2. In some embodiments, since the dielectric layer **140a** of the dielectric stack DS and the dielectric material **140b** include the same material (e.g., oxide), the dielectric layer **140a** of the dielectric stack DS and the dielectric material **140b** are collectively referred as a single dielectric layer (i.e., second dielectric layer **140** in FIG. 16B).

[0047] FIG. 4A is a top view of a step of manufacturing the memory device **100**, and FIG. 4B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 4A. Referring to FIGS. 4A and 4B, an opening O2 is formed downwards penetrating the dielectric material **140b**, the dielectric stack DS, the first conductive layer **130** and the insulating layer **120** in the discharge region DR. The opening O2 may expose the substrate **110** in the discharge region DR, and the opening O2 may be referred as a discharge via. In some embodiments, forming the opening O2 further includes etching a portion of the substrate **110** in the discharge region DR such that an exposed surface **110e** of the substrate **110** is below a top surface **111** of the substrate **110** (or a bottommost surface of the insulating layer **120**). In some embodiments, a patterned photoresist is formed on the dielectric material **140b**, in which the patterned photoresist may be formed by suitable deposition, development and/or etching techniques. Then, the dielectric material **140b** not covered by the patterned photoresist is etched by using the patterned photoresist as an etching mask to form the opening O2. After the opening O2 are formed, the patterned photoresist may be removed by using a photoresist stripping process (e.g., ashing process).

[0048] FIG. 5A is a top view of a step of manufacturing the memory device **100**, and FIG. 5B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 5A. Referring to FIGS. 5A and 5B, after forming the opening O2 in the discharge region DR, a conductive material **170'** is deposited over the dielectric material **140b**. Further, the conductive material **170'** fills the opening O1 in the staircase region SR and the opening O2 in the discharge region DR. In some embodiments, the opening O1 in the staircase region SR is not entirely filled by the conductive material **170'**, and the opening O2 in the discharge region DR is not entirely filled by the conductive material **170'**. With respect to the array region AR and the

staircase region SR, the conductive material **170'** is in contact with the dielectric material **140b**; and with respect to the discharge region DR, the conductive material **170'** is in contact with the dielectric material **140b**, the dielectric stack DS, the first conductive layer **130**, the insulating layer **120** and the substrate **110**. It is noted that a portion of the conductive material **170'** below the first conductive layer **130** in the discharge region DR may be referred as a discharge electrode **180** and other portions of the conductive material **170'** in the array region AR, in the staircase region SR and in the discharge region DR may be referred as a second conductive layer **170**. In greater details, the second conductive layer **170** is formed over the dielectric material **140b** in the array region AR and the staircase region SR. The second conductive layer **170** is formed over dielectric material **140b** and further extends from the dielectric material **140b** to the first conductive layer **130** in the discharge region DR. The discharge electrode **180** extends downward from the first conductive layer **130** and in electrical contact with the first conductive layer **130**.

[0049] FIG. 6A is a top view of a step of manufacturing the memory device **100**, and FIG. 6B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 6A. Referring to FIGS. 5A-5B and 6A-6B, after forming the conductive material **170'** (i.e., the second conductive layer **170** and the discharge electrode **180**), insulating structures **190** are filled in the opening O1 and opening O2. In greater details, the insulating structures **190** are formed over the second conductive layer **170** and the discharge electrode **180**, and then a planarization process is performed to remove excess materials of the insulating structures **190** such that a topmost surface **171** of the second conductive layer **170** is substantially coplanar with a top surface **191** of one of the insulating structures **190**. The planarization process may be a chemical mechanical planarization (CMP) process. In some embodiments, a bottom surface **193** of the insulating structures **190** in the staircase region SR is above the top surface **151** of the dielectric layer **150**. In some embodiments, a bottom surface **195** of the insulating structure **190** in the discharge region DR is below a bottom surface **133** of the first conductive layer **130**. In some embodiments, the insulating structures **190** include oxide. The insulating structures **190** and the dielectric material **140b** may include the same material. In some embodiments, the first conductive layer **130**, the conductive material **170'** (second conductive layer **170** and discharge electrode **180**) include the same material. For example, the first conductive layer **130** and the conductive material **170'** (second conductive layer **170** and discharge electrode **180**) include semiconductor materials (e.g., polysilicon).

[0050] FIG. 7A is a top view of a step of manufacturing the memory device **100**, and FIG. 7B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 7A. Referring to FIGS. 7A and 7B, a plurality of insulating layers **210** and a plurality of sacrificial material layers **220** are formed interlaced and stacked over the second conductive layer **170**. The insulating layers **210** and the sacrificial material layers **220** are alternately arranged or stacked over the second conductive layer **170**, and a bottommost layer of the insulating layers **210** closest to the second conductive layer **170** is in direct contact with the second conductive layer **170**. In some embodiments, the insulating layers **210** and the sacrificial material layers **220** include different dielectric materials. For example, the insulating layers **210** include oxide (e.g., silicon oxide), and the sacrificial material layers **220** include nitride (e.g., silicon nitride).

[0051] After forming the insulating layers **210** and the sacrificial material layers **220**, a plurality of memory structures MS are formed downwards penetrating through the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS and the first conductive layer **130** in the array region AR. In some embodiments, each of the memory structures MS has a portion embedded in the insulating layer **120**. Each of the memory structures MS includes a channel structure CH and a conductive plug **260** on the channel structure CH. Each of the channel structures CH includes a memory element **230**, a

channel layer **240**, and the dielectric filling structure **250**. The memory elements **230** are in contact with the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS, the first conductive layer **130** and the insulating layer **120**. The channel layers **240** are in contact with the memory elements **230**, and the channel layers **240** are disposed between the memory elements **230** and the dielectric filling structures **250**. In some embodiments, each of the memory elements **230** includes a blocking layer **232**, a memory storage layer **234**, and a tunneling layer **236**. The blocking layers **232** are formed using a conformal deposition method such that the blocking layers **232** line the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS, the first conductive layer **130**, and the insulating layer **120**. The memory storage layers **234** are formed on the blocking layers **232**, and the tunneling layers **236** are formed on the memory storage layers **234**. The blocking layers **232** and the tunneling layers **236** may include oxide (e.g., silicon oxide) or other suitable dielectric materials, and the memory storage layers **234** may include nitride (e.g., silicon nitride) or other material that is able to trap electrons. Accordingly, each of the memory elements **230** may be a tri-layer structure of an oxide layer, a nitride layer, and an oxide layer. The channel layers **240** may include polysilicon or other suitable semiconductor materials. The dielectric filling structures **250** may include oxide (e.g., silicon oxide) or other suitable dielectric materials. The conductive plugs **260** may include polysilicon or other suitable semiconductor materials. The conductive plugs **260** and the channel layers **240** may include the same conductive material, such as semiconductor materials or polysilicon.

[0052] In some embodiments, forming the memory structures MS include following steps. A plurality of openings O3 are formed downwards penetrating through the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS, and the first conductive layer **130** in the array region AR such that the insulating layer **120** is exposed. The memory elements **230** (including the blocking layers **232**, the memory storage layers **234**, and the tunneling layers **236**) are formed respectively in the openings O3, the channel layers **240** are then formed over the memory elements **230**, and the dielectric filling structures **250** are then formed over the channel layers **240**. As a result, the channel structures CH are formed. The channel structures CH are etched back, and the conductive plugs **260** are formed over the respective channel structures CH. As such, the memory structures MS are formed.

[0053] With respect to the staircase region SR, a plurality of support pillar structures **270** are formed downwards penetrating through the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS, and the first conductive layer **130**. In greater details, the insulating layers **210**, the sacrificial material layers **220**, the second conductive layer **170**, the dielectric material **140b**, the dielectric stack DS, and the first conductive layer **130** in the staircase region SR are etched in advance to form holes H1 exposing the insulating layer **120**. Then, dielectric materials are filled in the holes H1 to form the support pillar structures **270**. In some embodiments, each of the support pillar structures **270** has a portion embedded in the insulating layer **120**. In some embodiments, the support pillar structures **270** include oxide (e.g., silicon oxide) or other suitable dielectric materials. In some embodiments, forming the memory structures MS is performed prior to forming the support pillar structures **270**. In some embodiments, as shown in FIG. 7A, each of the memory structures MS has a circular top profile, and each of the support pillar structures **270** has a circular top profile. In some embodiments, as shown in FIG. 7A, a diameter of each of the support pillar structures **270** is greater than a diameter of each of the memory structures MS.

[0054] Thereafter, an insulating layer **280** is formed on the topmost layer of the insulating layers **210**. In some embodiments, the support pillar structures **270** and the insulating layer **280** may be formed together using a single deposition process. In other words, the support pillar structures **270**



and the insulating layer **280** include the same dielectric material. In some embodiments, the support pillar structures **270** and the insulating layer **280** include oxide (e.g., silicon oxide) or other suitable dielectric materials. In some embodiments, the support pillar structures **270**, the insulating layer **280**, and the insulating layers **210** include the same dielectric material, such as oxide.

[0055] In some embodiments, the first conductive layer **130**, the dielectric stack DS, the dielectric material **140b**, and the second conductive layer **170** are referred as a reference structure RS (or also referred as a buried source structure). As discussed above with respect to FIG. 5B, the discharge electrode **180** is below and connected to the first conductive layer **130** in the discharge region DR. The discharge electrode **180** extends downwards from a bottom surface **135** of the first conductive layer **130** of the reference structure RS and in electrical contact with the reference structure RS.

[0056] Now referring to FIGS. 17 and 18, FIG. 17 is a top view of the discharge electrode **180** according to some embodiments of the present disclosure, and FIG. 18 is a top view of the discharge electrode **180** according to some embodiments of the present disclosure. FIG. 17 and FIG. 18 illustrate different top views with respect to a region **200** (including the discharge electrode **180** and the insulating structures **190**) of FIG. 7B. As shown in FIG. 17, the insulating structure **190** has a rectangular top profile, and the discharge electrode **180** has a rectangular ring shape top profile that surrounds the insulating structure **190**. In some embodiments, as shown in FIG. 7B and FIG. 17, the second conductive layer **170** has a thickness T3 and the discharge electrode **180** has a width W1, in which a ratio of the thickness T3 of the second conductive layer **170** to the width W1 of the discharge electrode **180** is larger than 2. As shown in FIG. 18, the insulating structure **190** has a circular top profile, and the discharge electrode **180** has a circular ring shape top profile that surrounds the insulating structure **190**. In some embodiments, as shown in FIG. 7B and FIG. 18, the second conductive layer **170** has the thickness T3 and the discharge has a diameter D1, in which a ratio of the thickness T3 of the second conductive layer **170** to the diameter D1 of the discharge electrode **180** is larger than 2.

[0057] Now referring to FIG. 19, FIG. 19 is a partially cross-sectional view of a discharge electrode **180a** in the discharge region DR according to some embodiments of the present disclosure. The discharge electrode **180a** of FIG. 19 is substantially the same as the discharge electrode **180** of FIG. 7B, and the difference is a profile of the discharge electrode **180a**. As shown in FIG. 19, the discharge electrode **180a** entirely fills the opening O2 such that there is no insulating structure (i.e., insulating structure **190** in the discharge region DR of FIG. 7B) within or surrounded by the discharge electrode **180a**.

[0058] Now referring to FIGS. 20 and 21, FIG. 20 is a top view of the discharge electrode **180a** of FIG. 19 according to some embodiments of the present disclosure, and FIG. 21 is a top view of the discharge electrode **180a** of FIG. 19 according to some embodiments of the present disclosure. FIG. 20 and FIG. 21 illustrate different top views with respect to the discharge electrode **180a** of FIG. 19. As shown in FIG. 20, the discharge electrode **180** has a rectangular top profile. In some embodiments, as shown in FIG. 19 and FIG. 20, the second conductive layer **170** has the thickness T3 and the discharge electrode **180a** has a width W2, in which a ratio of the thickness T3 of the second conductive layer **170** to the width W2 of the discharge electrode **180a** is smaller than 2. As shown in FIG. 21, the discharge electrode **180** has a circular top profile. In some embodiments, as shown in FIG. 19 and FIG. 21, the second conductive layer **170** has the thickness T3 and the discharge electrode **180a** has a diameter D2, in which a ratio of the thickness T3 of the second conductive layer **170** to the diameter D2 of the discharge electrode **180a** is smaller than 2.

[0059] FIG. 8A is a top view of a step of manufacturing the memory device **100**, and FIG. 8B is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. 8A. Referring to FIGS. 8A and 8B, the insulating layers **210**, the sacrificial material layers **220**, and the second conductive layer **170** are etched to form slit trenches ST downwards penetrating through the insulating layers **210**, the sacrificial material layers **220**, and the second

conductive layer **170** in the array region AR and the staircase region SR. The slit trenches ST expose the second conductive layer **170** in the array region AR and the staircase region SR. In some embodiments, an exposed surface **173** of the second conductive layer **170** is below a topmost surface of the dielectric material **140b** in the staircase region SR. Further, the exposed surface **173** of the second conductive layer **170** is below a top surface of the dielectric layer **150** in the staircase region SR. In some embodiments, forming the slit trenches ST further includes removing an entirety of the insulating structure **190** in the staircase region SR. In some embodiments, a depth of the slit trenches ST in the array region AR is smaller than a depth of the slit trenches ST in the staircase region SR.

[0060] In some embodiments, as shown in FIG. **8A**, each of the slit trenches ST extends between the array region AR and the staircase region SR and extends along the first direction X. In some embodiments, as discussed above with respect to FIG. **1A**, the opening **O1** corresponding to a bottom of the dielectric material **140b** includes the first portions **O1a** along the first direction X and the second portion **O1b** along the second direction Y. The slit trenches ST are parallel with and overlap with the respective first portions **O1a** of the opening **O1**. The second portion **O1b** of the opening **O1** is disposed between the memory structures MS and the support pillar structures **270**.

[0061] FIG. **9A** is a top view of a step of manufacturing the memory device **100**, and FIG. **9B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **9A**. Referring to FIGS. **9A** and **9B**, a protective layer **290** is conformally formed on the structure of FIGS. **8A** and **8B**. In greater details, the protective layer **290** is formed using a conformal deposition method such that the protective layer **290** lines the insulating layer **280**, the insulating layers **210**, the sacrificial material layers **220** and the second conductive layer **170** in the array region AR and the staircase region SR. After forming the protective layer **290**, a spacer layer **300** is formed conformally on the protective layer **290**. The protective layer **290** and the spacer layer **300** are configured to prevent the sidewalls of the slit trenches ST (e.g., the sidewalls of the insulating layers **210** and the sidewalls of the sacrificial material layers **220**) from damaging in subsequent etching processes (e.g., etching process of the dielectric stack DS and dielectric material **140b** in FIGS. **12A-13B**). In some embodiments, the protective layer **290**, the second conductive layer **170** and/or the first conductive layer **130** include the same conductive material. In some embodiments, the spacer layer **300** and the protective layer **290** includes different material. For example, the protective layer **290** includes semiconductor materials (e.g., polysilicon), and the spacer layer **300** includes the dielectric materials (e.g., oxide). In some embodiments, the spacer layer **300** and the insulating layer **280** include the same dielectric material.

[0062] FIG. **10A** is a top view of a step of manufacturing the memory device **100**, and FIG. **10B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **10A**. Referring to FIGS. **10A** and **10B**, after forming the protective layer **290** and the spacer layer **300**, one or more etching processes are performed to further extend (or deepen) the slit trenches ST such that the first conductive layer **130** is exposed. With respect to the array region AR, the spacer layer **300**, the protective layer **290**, the second conductive layer **170**, the dielectric material **140b** and the dielectric stack DS (the dielectric layers **140a** and **150**) are etched from the slit trenches ST, and the etching process(es) may be stopped at the first conductive layer **130**. With respect to the staircase region SR, the spacer layer **300**, the protective layer **290**, the second conductive layer **170** and the dielectric material **140b** are etched from the slit trenches ST, and the etching process(es) may be stopped at the first conductive layer **130**. In some embodiments, a portion of the first conductive layer **130** in the array region AR and/or the staircase region SR is etched such that an exposed surface of the first conductive layer **130** is below the topmost surface **131** of the first conductive layer **130**.

[0063] In some embodiments, the slit trenches ST expose sidewalls of the dielectric material **140b**

and sidewalls of the dielectric stack DS (i.e., the dielectric layer **140a** and **150**) in the array region AR. Further, the slit trenches ST expose sidewalls **177** of the second conductive layer **170** and sidewalls **147** of the dielectric material **140b** in the staircase region SR. In some embodiments, the one or more etching processes of deepening the slit trenches ST are performed by using a dry etching process, a wet etching process, or a combination thereof. Since the dielectric material **140b** covering the sidewall of the dielectric stack DS and the second conductive layer **170** on the dielectric material **140b** in the staircase region SR protect the adjacent dielectric stack DS, the dielectric stack DS in the staircase region SR is not exposed (i.e., covered by the dielectric material **140b** and the second conductive layer **170**) during deepening the slit trenches ST. Further, a damage of the support pillar structure **270** during etching the dielectric stack DS (i.e., the etching processes in FIGS. **12A-12C** and **13A-13B**) will be avoided or prevented, thereby avoiding deformation or collapse problems.

[0064] FIG. **11A** is a top view of a step of manufacturing the memory device **100**, and FIG. **11B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **11A**. Referring to FIGS. **11A** and **11B**, a selectively oxidation process is performed on an exposed portion of the protective layer **290**, an exposed portion of the second conductive layer **170**, and an exposed portion of the first conductive layer **130** through the slit trenches ST in the array region AR and the staircase region SR to form oxide structures **310a** and **310b**. In greater details, the selectively oxidation process is performed to selective oxidize semiconductor material (e.g., polysilicon). The exposed portions of the semiconductor material layers (i.e., the protective layer **290**, the second conductive layer **170**, and the first conductive layer **130**) are oxidized and are converted to the oxide structures **310a** and **310b** including semiconductor oxide (e.g., silicon oxide). On the other hand, exposed portions of the spacer layer **300**, the dielectric layer **140a**, the dielectric layer **150**, and the dielectric material **140b** are not oxidized since the spacer layer **300**, the dielectric layer **140a**, the dielectric layer **150**, and the dielectric material **140b** include dielectric material. In some embodiments, the oxide structure **310a** covers the exposed portion of the protective layer **290** and the exposed portion of the second conductive layer **170** adjacent to the slit trenches ST. Similarly, the oxide structure **310b** covers the exposed portion of the first conductive layer **130** adjacent to the slit trenches ST. In some embodiments, the selectively oxidation process includes wet or dry thermal oxidation in an ambient including an oxide, H.sub.2O, NO, combinations thereof, or the like. In some embodiments, the selectively oxidation process includes an in-situ steam generation (ISSG) process in an ambient environment of oxide, H.sub.2O, NO, combinations thereof, or the like.

[0065] FIG. **12A** is a top view of a step of manufacturing the memory device **100**, FIG. **12B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **12A**, and FIG. **12C** is a cross-sectional view taking along line X1-X1' of FIG. **12A**. Referring to FIGS. **11A-11B** and **12A-12C**, an etching process is performed to remove a portion of the dielectric layer **150** of the dielectric stack DS in the array region AR. In other words, an entirety of the dielectric layer **150** of the dielectric stack DS in the array region AR is removed to form a recess R1 communicated with the slit trenches ST. In some embodiments, the dielectric layer **150** has lower etching resistance to the etching process than the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300** and the oxide structures **310a-310b**. As a result, the dielectric layer **150** is etched and the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300** and the oxide structures **310a-310b** are kept substantially intact (not etched) during the etching process. Further, since the oxide structure **310a** covers the second conductive layer **170** and the protective layer **290** and the oxide structure **310b** covers the first conductive layer **130**, the damage of the first conductive layer **130**, the second conductive layer **170** and the protective layer **290** during the etching process can be avoided. In some embodiments, the recess R1 exposes the

dielectric layer **140a** and the dielectric material **140b**. In some embodiments, since the dielectric material **140b** disposed between a sidewall **153** of the dielectric layer **150** and a sidewall **179** of the second conductive layer **170** in the staircase region SR (i.e., the dielectric material **140b** covers the sidewall of the dielectric layer **150** in the staircase region SR), the dielectric material **140b** may protect the dielectric layer **150** in the staircase region SR during the etching process. In some embodiments, the etching process of removing the dielectric layer **150** includes a wet etching process, in which the wet etching process may use phosphoric acid solution or other suitable acidic etching solutions.

[0066] FIG. **13A** is a top view of a step of manufacturing the memory device **100**, and FIG. **13B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **13A**. Referring to FIGS. **13A** and **13B**, an etching process is performed to remove an entirety of the dielectric layer **140a** and the dielectric material **140b** in the array region AR such that the recess R1 is expanded. The etching process further removes the spacer layer **300** and the oxide structures **310a-310b**. In some embodiments, the etching process further removes the memory elements **230** of the memory structures MS through the recess R1 to expose the channel layers **240** of the memory structures MS in the array region AR. In some embodiments, the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300**, the oxide structures **310a-310b**, and the memory elements **230** have lower etching resistance to the etching process than the first conductive layer **130**, the second conductive layer **170**, and the protective layer **290**. As a result, the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300**, the oxide structures **310a-310b**, and the memory elements **230** are etched and the first conductive layer **130**, the second conductive layer **170** and the protective layer **290** are kept substantially intact (not etched) during the etching process. In some embodiments, etchants of the etching process of FIGS. **13A-13B** are different from etchants of the etching process of FIGS. **12A-12C**. In some embodiments, the recess R1 exposes the first conductive layer **130** and the second conductive layer **170** in the array region AR. In some embodiments, the etching process of removing the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300**, the oxide structures **310a-310b**, and the memory elements **230** includes a dry etching process, a wet etching process, or a combination thereof. In some embodiments, since the dielectric layer **140a**, the dielectric material **140b**, the spacer layer **300**, and the oxide structures **310a-310b** include the same dielectric material (e.g., oxide), they can be removed in a single selective etching process.

[0067] As shown in FIGS. **12A-12C** and **13A-13B**, the dielectric stack DS (i.e., the dielectric layers **140a** and **150**) includes a first portion in the staircase region SR and a second portion in the array region AR, and the dielectric material **140b** includes a first portion in the staircase region SR and a second portion in the array region AR. The etching processes of FIGS. **12A-12C** and **13A-13B** are performed to remove the second portion of the dielectric stack DS (i.e., the dielectric layers **140a** and **150**) in the array region AR to expose the memory structures MS, and the first portion of the dielectric stack DS (i.e., the dielectric layers **140a** and **150**) in the staircase region SR remains after the etching processes of FIGS. **12A-12C** and **13A-13B** are complete. In some embodiments, since the dielectric material **140b** covers the sidewalls of the dielectric layer **150** and the sidewalls of the dielectric layer **140a** and the second conductive layer **170** covers a sidewall of the dielectric material **140b**, the dielectric stack DS (i.e., the dielectric layers **140a** and **150**) in the staircase region SR is kept substantially intact (not etched) during the etching processes of FIGS. **12A-12C** and **13A-13B**. As a result, the damage of the support pillar structure **270** during the etching processes of FIGS. **12A-12C** and **13A-13B** can be avoided or prevented, thereby avoiding deformation or collapse problems. Further, the etching processes of FIGS. **12A-12C** and **13A-13B** are performed to remove the second portion of the dielectric material **140b** in the array region AR to expose the memory structures MS, and the first portion of the dielectric material **140b** in the staircase region SR remain after the etching processes are complete. In some embodiments, since

the dielectric material **140b** has lower etching resistance than the first conductive layer **130** and the second conductive layer **170**, the dielectric material **140b** in the staircase region SR is laterally etched to form at least one gap G1 vertically between the first conductive layer **130** and the second conductive layer **170**.

[0068] FIG. **14A** is a top view of a step of manufacturing the memory device **100**, and FIG. **14B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **14A**. Referring to FIGS. **14A** and **14B**, conductive materials CM are formed on the protective layer **290** and the sidewalls of the slit trenches ST. The conductive material CM further include a first portion **320'** filled in the recess R1 and a second portion **322'** filled in the gap G1 (see FIG. **13B**). The first portion **320'** is in contact with the memory structures MS in the array region AR and the second portion **322'** is in contact with the dielectric material **140b**. The first portion **320'** may be referred as a bottom electrode layer (e.g., bottom electrode layer **320** in FIG. **15B**) described in more detail below and the second portion **322'** may be referred as a conductive material (e.g., conductive material **322** in FIG. **15B**) described in more detail below. In some embodiments, the conductive materials CM include semiconductor materials (e.g., polysilicon). In some embodiments, the conductive materials CM, the protective layer **290**, the second conductive layer **170** and/or the first conductive layer **130** include the same conductive material.

[0069] FIG. **15A** is a top view of a step of manufacturing the memory device **100**, and FIG. **15B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **15A**. Referring to FIGS. **14A-14B** and **15A-15B**, performing an etching process to pattern the conductive materials CM such that the bottom electrode layer **320** is formed (or defined) in electrical contact with the channel layers **240** of the memory structures MS and the conductive material **322** in contact with the dielectric material **140b**. In greater details, as shown in FIGS. **14B** and **15B**, the etching process removes portions of the conductive materials CM over the insulating layer **280** and in the slit trenches ST. The etching process further entirely removes the protective layer **290** in the array region AR and the staircase region SR. In some embodiments, after the etching process is complete, the first conductive layer **130** in the array region AR and the staircase region SR is exposed through the slit trenches ST. Further, the top surface **281** of the insulating layer **280**, the sidewalls of the insulating layers **210**, the sidewalls of the sacrificial material layers **220**, and the sidewalls of the second conductive layer **170** in the array region AR and the staircase region SR are exposed. In some embodiments, since the conductive materials CM and the protective layer **290** include the same conductive material (e.g., polysilicon or other suitable semiconductor materials), the conductive materials CM and the protective layer **290** may be removed in a single selective etching process. In some embodiments, the conductive materials CM and the protective layer **290** are removed using a wet etching process.

[0070] It is noted that the dielectric layer **140a** and the dielectric material **140b** are collectively referred as a single dielectric layer **140** described in more detail in FIGS. **16A-16C** since the dielectric layer **140a** and the dielectric material **140b** include the same material (e.g., oxide).

[0071] FIG. **16A** is a top view of a step of manufacturing the memory device **100**, and FIG. **16B** is a cross-sectional view of the memory device **100** including the array region AR, the staircase region SR, and the discharge region DR respectively taken along line Y1-Y1', line Y2-Y2', and line Y3-Y3' in FIG. **16A**. Referring to FIGS. **15A-15B** and **16A-16B**, the sacrificial material layers **220** are replaced with a plurality of conductive layers **350**. In greater details, an entirety of the sacrificial material layers **220** is removed to form recesses R2 such that the recesses R2 are communicated with the slit trenches ST. In some embodiments, the sacrificial material layers **220** are removed using a wet etching process, in which the wet etching process may use phosphoric acid solution or other suitable acidic etching solutions. In some embodiments, the support pillar structures **270** provide the structural support to prevent the memory device **100** from collapsing

during the removal of the sacrificial material layers **220**.

[0072] After removing the sacrificial material layers **220** to form the recesses **R2**, conductive materials are filled in the recesses **R2** and then performing an etching process to remove the excess conductive materials so as to form the conductive layers **350**. The conductive layers **350** may be referred to as gate layers or word lines. Specifically, the conductive layers **350** may be used as control gate electrodes of the memory device **100** (in particular with a vertical NAND memory device). The insulating layers **210** and conductive layers **350** are collectively referred to as a stacked structure **400** over the second conductive layer **170** of reference structure **RS**. In some embodiments, filling conductive materials in the recesses **R2** is performed by using a chemical vapor deposition, an atomic layer deposition, a physical vapor deposition, an electroless plating process, or other suitable deposition processes. In some embodiments, the conductive layers **350** include metal (e.g., tungsten) or other suitable conductive materials.

[0073] After the sacrificial material layers **220** are replaced with the conductive layers **350**, wall structures **WS** are formed in the slit trenches **ST**. In greater details, each of the wall structures **WS** includes a conductive material **340** with an insulating material **330** on sidewalls. The insulating material **330** may be formed in the slit trenches **ST** by using a deposition process, and then the conductive material **340** is filled in the slit trenches **ST**. The insulating material **330** may be formed by using a chemical vapor deposition process, an atomic layer deposition process, a physical vapor deposition process or other suitable deposition processes. The insulating material **330** includes oxide (e.g., silicon oxide) or other suitable dielectric materials. In some embodiments, the insulating material **330**, the insulating layer **280** and/or the insulating layers **210** include the same material (e.g., oxide). In some embodiments, the conductive material **340** is formed by using a chemical vapor deposition process, an atomic layer deposition process, a physical vapor deposition process, or other suitable deposition processes. The conductive material **340** may include semiconductor material (e.g., polysilicon), metal or other suitable conductive materials. In some embodiments, the conductive material **340**, the conductive plug **260**, the bottom electrode layer **320**, the conductive material **322**, the first conductive layer **130** and/or the second conductive layer **170** include the same material, such as polysilicon.

[0074] In some embodiments, a planarization process (e.g., a chemical mechanical polishing process) is performed to remove excess materials of the insulating material **330** and/or the conductive material **340**. For example, the insulating layer **280** serves as an etching stop layer for performing the planarization process, such that a top surface of each of the wall structures **WS** (i.e., a top surface of the conductive material **340** and a top surface of the insulating material **330**) is substantially coplanar with the top surface **281** of the insulating layer **280**.

[0075] In some embodiments, the wall structures **WS** are located on the sidewalls of the conductive layers **350**, the sidewalls of the insulating layers **210**, and the sidewalls of the second conductive layer **170**. In other words, the wall structures **WS** downwards penetrate through the conductive layers **350**, the insulating layers **210**, and the second conductive layer **170**. Further, each of the wall structures **WS** has a lower portion embedded in the first conductive layer **130**. In some embodiments, the insulating material **330** is configured to separate the conductive material **340** from the conductive layers **350** to avoid an electrical contact between the conductive material **340** and the conductive layers **350**. The conductive material **340** of each of the wall structures **WS** is in electrical contact with the first conductive layer **130** in the array region **AR** and the staircase region **SR**.

[0076] As shown in FIGS. **16A** and **16B**, the memory device **100** includes the array region **AR**, the staircase region **SR** adjacent to the array region **AR** and the discharge region **DR** disposed in either array region **AR** (a region in array region **AR** without wall structures **WS**) or the staircase region **SR** (a region in staircase region **SR** without support pillar structures **270**). The memory device **100** further includes the reference structure **RS**, the stacked structure **400** and the wall structures **WS**. The reference structure **RS** includes the conductive structure **RSC** and the dielectric structure **RSD**

embedded within the conductive structure RSC in the staircase region SR. The dielectric structure RSD includes the first dielectric layer **150** and the second dielectric layer **140** disposed on the top surface **151**, the sidewall **153**, and a bottom surface **155** of the first dielectric layer **150**. The sidewall **153** of the first dielectric layer **150** is connected to the top surface **151** and the bottom surface **155** of the first dielectric layer **150**. In other words, the second dielectric layer **140** extends from the top surface **151** of the first dielectric layer **150**, passing through the sidewall **153** of the first dielectric layer **150**, to the bottom surface **155** of the first dielectric layer **150**. The stacked structure **400** includes the conductive layers **350** and the insulating layers **210** alternately stacked over the reference structure RS. The wall structures WS penetrate the stacked structure **400** and beyond the dielectric structure RSD. It is noted that the term of “beyond” herein means that a bottommost surface of the wall structures WS is below a bottommost surface **143** of the dielectric structure RSD along the direction perpendicular to the plane defined by the first direction X and the second direction Y. The wall structures WS are in electrical contact with the reference structure RS. [0077] In some embodiments, as shown in FIG. **16B**, the dielectric structure RSD is vertically between the first conductive layer **130** and the second conductive layer **170** along the direction perpendicular to a plane defined by the first direction X and the second direction Y. In some embodiments, with respect to the staircase region SR, the second dielectric layer **140** is in contact with the conductive structure RSC, while the first dielectric layer **150** is separated from the conductive structure RSC by the second dielectric layer **140**.

[0078] In some embodiments, the conductive structure RSC of the reference structure RS includes the first conductive layer **130**, the second conductive layer **170**, the bottom electrode layer **320** and the conductive material **322**. The first conductive layer **130** is disposed under the dielectric structure RSD, and the second conductive layer **170** is disposed over the first conductive layer **130**. The bottom electrode layer **320** is vertically between the first conductive layer **130** and the second conductive layer **170** in the array region AR, and the bottom electrode layer **320** is in electrical contact with the first conductive layer **130**, the second conductive layer **170** and the channel layers **240** of the memory structures MS. The conductive material **322** is vertically between the first conductive layer **130** and the second conductive layer **170** in the staircase region SR along the direction perpendicular to the plane defined by the first direction X and the second direction Y, and the conductive material **322** is laterally between the dielectric structure RSD and the wall structures WS along the second direction Y. In some embodiments, the dielectric structure RSD is disposed between the first conductive layer **130** and the second conductive layer **170** in the staircase region SR. In some embodiments, the second conductive layer **170** includes a first portion **172** along a top surface RSD1 of the dielectric structure RSD and a second portion **174** along a sidewall RSD2 of the dielectric structure RSD in the staircase region SR. The second portion **174** of the second conductive layer **170** is in contact with the dielectric structure RSD and one of the wall structures WS. The second portion **174** of the second conductive layer **170** has an L-shaped cross-section. The second dielectric layer **140** of the dielectric structure RSD is in contact with a sidewall **178** of the second portion **174** of the second conductive layer **170**.

[0079] In some embodiments, the second dielectric layer **140** of the dielectric structure RSD covers the top surface **151** of the first dielectric layer **150**, the sidewall **153** of the first dielectric layer **150**, and the bottom surface **155** of the first dielectric layer **150**. In some embodiments, the second dielectric layer **140** includes a first portion **142** over the top surface **151** of the first dielectric layer **150**, a second portion **144** under the bottom surface **155** of the first dielectric layer **150** and an extension portion **146** extending from the first portion **142** to the second portion **144**. The first portion **142** of the second dielectric layer **140** is in parallel with the second portion **144** of the second dielectric layer **140**. The extension portion **146** of the second dielectric layer **140** extends downward from a bottom surface **145** of the second dielectric layer **140**. The extension portion **146** of the second dielectric layer **140** extends to the bottom surface **175** of the second portion **174** of the second conductive layer **170**. The extension portion **146** of the second dielectric layer **140** has

an L-shaped cross-section. In some embodiments, the bottommost surface **143** of the extension portion **146** of the second dielectric layer **140** of the dielectric structure RSD is below the topmost surface **131** of the first conductive layer **130**. In some embodiments, a material (e.g., nitride) of the first dielectric layer **150** is different from a material (e.g., oxide) of the second dielectric layer **140**. [0080] In some embodiments, the memory device **100** further includes memory structures MS in the array region AR, the support pillar structure **270** in the staircase region SR and the discharge electrode **180** in the discharge region DR. The memory structures MS downwards penetrate through the conductive layers **350**, the insulating layers **210**, and the reference structure RS and extend to the insulating layer **120** in the array region AR. The memory structures MS are in electrical with the bottom electrode layer **320** of the reference structure RS. The support pillar structures **270** downwards penetrate through the conductive layers **350**, the insulating layers **210**, and the reference structure RS and extend to the insulating layer **120** in the staircase region SR. Each of the support pillar structures **270** include a lower portion surrounded by the first conductive layer **130**, the dielectric structure RSD and the second conductive layer **170** of the reference structure RS. The discharge electrode **180** extends downwards from the bottom surface **135** of the first conductive layer **130** of the reference structure RS and in electrical contact with the reference structure RS. In some embodiments, the dielectric structure RSD is in contact with one of the support pillar structures **270** and spaced apart from the wall structures WS. In other words, the dielectric structure RSD is separated from the wall structures WS by the second portion **174** of the second conductive layer **170**.

[0081] In some embodiments, as shown in FIG. **16A**, the memory structures MS are arranged in multiple rows along the second direction Y, in which the memory structures MS may be referred as vertical NAND memory strings. The wall structures WS extend along the first direction X in the array region AR and the staircase region SR. The memory structures MS is disposed in the array region AR and the support pillar structures **270** is disposed in the staircase region SR. The wall structures WS are configured to divide the memory device **100** into multiple blocks. For example, the memory structures MS and the support pillar structures **270** between the two adjacent wall structures WS are referred as one block.

[0082] FIG. **22** is a cross-sectional view of the memory device **100** including metal layers **430** and a passivation layer **440** according to some embodiments of the present disclosure. The memory device **100** further includes conductive features **410**, an insulating layer **420**, the metal layer **430**, and the passivation layer **440**. The conductive features **410** may include multiple conductive features **412**, **414**, and **416** formed on the memory structures MS and the wall structures WS in the array region AR. The conductive features **412** are in electrical contact with the memory structures MS or the wall structures WS in the array region AR, the conductive features **414** are formed on and in electrical contact with the conductive features **412**, and the conductive features **416** are formed on and in electrical contact with the conductive features **414**. The insulating layer **420** is formed on the insulating layer **280** and surrounds the conductive features **410**. The metal layers **430** are formed on the insulating layer **420** in the array region AR, the staircase region SR, and the discharge region DR. The passivation layer **440** is formed on the metal layers **430** in the array region AR, the staircase region SR, and the discharge region DR. The passivation layer **440** has a portion **442** in contact with sidewalls of the metal layers **430**.

[0083] In some embodiments, the substrate **110** is referred as a circuit under array layer. The substrate **110** includes device structures **112**, an interconnect structure, and bonding structure. The device structures **112** are active devices (e.g., transistors). The interconnect structure is connected to the device structures **112**, and the interconnect structure includes conductive lines **113** that provide interconnections (wiring) between the device structures **112**, and between conductive lines **113** themselves. The conductive lines **113** may be insulated from each other by inter-metal dielectric (IMD) layers **114**. The interconnect structure may further include various conductive features **115** located within the IMD layers **114** for connecting the conductive lines **113**. The



bonding structure of the substrate **110** includes bonding pads **116a** and **116b** and dielectric material **117a** and **117b**. The bonding structure of the substrate **110** may further include a bonding feature **118** connecting the bonding pads **116a** and **116b**.

[0084] FIG. **23** is a cross-sectional view of the memory device **100** including metal layers **430a** and a passivation layer **440a** according to some embodiments of the present disclosure. The memory device **100** further includes the conductive features **410**, the insulating layer **420**, the metal layer **430a**, the passivation layer **440a**, a conductive feature **450**, and a substrate **500**. The conductive features **410** may include multiple conductive features **412**, **414**, and **416** formed on the memory structures MS and the wall structures WS in the array region AR. The insulating layer **420** is formed on the insulating layer **280** and surrounds the conductive features **410**. The metal layers **430a** are formed on a backside side **110b** of the substrate **110** in the array region AR, the staircase region SR and the discharge region DR. The passivation layer **440** is formed the backside side **110b** of the substrate **110** and under the metal layers **430**. The conductive feature **450** is in electrical contact with the first conductive layer **130** and the metal layer **430a**.

[0085] In some embodiments, the substrate **500** is disposed over the stacked structure **400** (i.e., over a front side **110f** of the substrate **110**). The substrate **500** includes device structures **512**, an interconnect structure and bonding structure. The device structures **512** are active devices (e.g., transistors). The interconnect structure is connected to the device structures **512**, and the interconnect structure includes conductive lines **513** that provide interconnections (wiring) between the device structures **512**, and between conductive lines **513** themselves. The conductive lines **513** may be insulated from each other by inter-metal dielectric (IMD) layers **514**. The interconnect structure may further include various conductive features **515** located within the IMD layers **514** for connecting the conductive lines **513**. The bonding structure of the substrate **500** includes bonding pads **516a** and **516b** and dielectric material **517a** and **517b**. In some embodiments, the substrate **500** is bonded on the stacked structure **400** by a hybrid bonding process. The hybrid bonding process involves at least two bonding types, including metal-to-metal bonding and non-metal-to-non-metal bonding. For example, the bonding pads **516a** and the bonding pads **516b** are bonded by metal-to-metal bonding, and the dielectric material **517a** and the dielectric material **517b** are bonded by non-metal-to-non-metal bonding.

[0086] According to the aforementioned embodiments of the present disclosure, since the reference structure includes a conductive structure and the dielectric structure embedded within the conductive structure in the staircase region, the damage of the support pillar structure during etching processes (e.g., the etching process of exposing the channel layer of the memory structure) can be avoided or prevented, thereby avoiding deformation or collapse problems.

[0087] Although the present disclosure has been described in considerable detail with reference to certain embodiments thereof, other embodiments are possible. Therefore, the spirit and scope of the appended claims should not be limited to the description of the embodiments contained herein.

[0088] It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present disclosure without departing from the scope or spirit of the disclosure. In view of the foregoing, it is intended that the present disclosure covers modifications and variations of this disclosure provided they fall within the scope of the following claims.

## Claims

**1.** A memory device, comprising: an array region and a staircase region; a reference structure disposed in the array region and the staircase region, the reference structure comprising a conductive structure and a dielectric structure embedded within the conductive structure in the staircase region, wherein the dielectric structure comprises: a first dielectric layer; and a second dielectric layer disposed on a top surface of the first dielectric layer, a sidewall of the first dielectric layer and a bottom surface of the first dielectric layer, wherein the sidewall of the first dielectric

layer is connected to the top surface of the first dielectric layer and the bottom surface of the first dielectric layer; a stacked structure comprising a plurality of conductive layers and a plurality of insulating layers alternately stacked over the reference structure, and the stacked structure disposed in the array region and the staircase region; and a wall structure extending along a direction from the array region to the staircase region, penetrating the stacked structure and beyond the dielectric structure.

**2.** The memory device of claim 1, wherein the conductive structure comprises: a first conductive layer under the dielectric structure; and a second conductive layer over the first conductive layer, the second conductive layer including a first portion along a top surface of the dielectric structure and a second portion along a sidewall of the dielectric structure in the staircase region.

**3.** The memory device of claim 2, wherein a bottommost surface of the second dielectric layer of the dielectric structure is below a topmost surface of the first conductive layer.

**4.** The memory device of claim 2, further comprising: a discharge electrode extending downwards from a bottom surface of the first conductive layer and in electrical contact with the reference structure.

**5.** The memory device of claim 2, wherein the second dielectric layer of the dielectric structure is in contact with a sidewall of the second portion of the second conductive layer.

**6.** The memory device of claim 2, wherein a portion of the second dielectric layer of the dielectric structure extends to a bottom surface of the second portion of the second conductive layer.

**7.** The memory device of claim 1, further comprising: a substrate over the stacked structure.

**8.** The memory device of claim 1, wherein the wall structure is in electrical contact with the reference structure.

**9.** The memory device of claim 1, further comprises: a discharge electrode extending downwards from a bottom surface of the reference structure and in electrical contact with the reference structure in a discharge region.

**10.** The memory device of claim 9, wherein the conductive structure comprises: a first conductive layer; and a second conductive layer over the first conductive layer, wherein a ratio of a thickness of the second conductive layer to a width of the discharge electrode is larger than 2.

**11.** The memory device of claim 1, wherein the first dielectric layer and the second dielectric layer comprise different materials.

**12.** A memory device, comprising: a reference structure including a conductive structure and a dielectric structure embedded within the conductive structure, wherein the dielectric structure comprises: a first dielectric layer; and a second dielectric layer, wherein the second dielectric layer has an extension portion extending downward from a bottom surface of the second dielectric layer; a stacked structure including a plurality of conductive layers and a plurality of insulating layers alternately stacked over the reference structure; and a wall structure penetrating the stacked structure and beyond the dielectric structure.

**13.** The memory device of claim 12, wherein the second dielectric layer of the dielectric structure covers a top surface of the first dielectric layer, a sidewall of the first dielectric layer and a bottom surface of the first dielectric layer.

**14.** The memory device of claim 12, wherein the extension portion of the second dielectric layer of the dielectric structure has an L-shaped cross-section.

**15.** The memory device of claim 12, wherein the conductive structure comprises: a first conductive layer; and a second conductive layer over the first conductive layer, wherein the dielectric structure is between the first conductive layer and the second conductive layer.

**16.** The memory device of claim 15, further comprising: a discharge electrode extending downwards from the first conductive layer and in electrical contact with the reference structure.

**17.** The memory device of claim 15, wherein a bottommost surface of the extension portion of the second dielectric layer of the dielectric structure is below a topmost surface of the first conductive layer.

**18.** The memory device of claim 12, further comprising: a discharge electrode extending downwards from the reference structure and in electrical contact with the reference structure.

**19.** The memory device of claim 12, wherein the wall structure comprises a conductive material with an insulating material on sidewalls.

**20.** A manufacturing method of a memory device, comprising: forming a first conductive layer and a dielectric stack in an array region and a staircase region of the memory device; forming an opening in a first portion of the dielectric stack in the staircase region; depositing a dielectric material over the dielectric stack and lining the opening; forming a second conductive layer over the dielectric material and filling the opening; forming insulating layers and sacrificial material layers alternately stacked over the second conductive layer; forming a memory structure through the insulating layers, the sacrificial material layers, the second conductive layer, the dielectric stack and the first conductive layer in the array region; forming a slit trench through the insulating layers, the sacrificial material layers and the second conductive layer in the array region and the staircase region, wherein the slit trench exposes a sidewall of the second conductive layer and a sidewall of the dielectric material in the staircase region; performing an etching process to remove a second portion of the dielectric stack in the array region to expose the memory structure, wherein the first portion of the dielectric stack in the staircase region remains after the etching process is complete; forming a bottom electrode layer in electrical contact with the memory structure; and replacing the sacrificial material layers with conductive layers.

---