

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285962

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

LIANG; Shuen-Shin et al.

SEMICONDUCTOR DEVICE AND METHOD FOR MANUFACTURING THE SAME

Abstract

A method for manufacturing a semiconductor device includes: forming a lower metal contact in a trench of a first dielectric structure, the lower metal contact having a height less than a depth of the trench and being made of a first metal material; forming an upper metal contact to fill the trench and to be in contact with the lower metal contact, the upper metal contact being formed of a second metal material different from the first metal material and having a bottom surface with a dimension the same as a dimension of a top surface of the lower metal contact; forming a second dielectric structure on the first dielectric structure; and forming a via contact penetrating through the second dielectric structure to be electrically connected to the upper metal contact, the via contact being formed of a metal material the same as the second metal material.

Inventors: LIANG; Shuen-Shin (Hsinchu, TW), CHU; Chia-Hung (Hsinchu, TW), CHANG; Po-Chin (Hsinchu, TW), CHEN; Tzu-Pei (Hsinchu, TW), CHANG; Ken-Yu (Hsinchu, TW), HUANG; Hung-Yi (Hsinchu, TW), CHIEN; Harry (Hsinchu, TW), LOH; Wei-Yip (Hsinchu, TW), TSAI; Chun-I (Hsinchu, TW), LEE; Hong-Mao (Hsinchu, TW), WANG; Sung-Li (Hsinchu, TW), LIN; Pinyen (Hsinchu, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Family ID: 87161150

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 19/217660

Filed: May 23, 2025

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01L23/522** (20060101); **H01L21/768** (20060101); **H10D64/01** (20250101)

U.S. Cl.:

CPC **H01L23/5226** (20130101); **H01L21/76843** (20130101); **H01L21/76877** (20130101); **H10D64/01** (20250101);

Background/Summary

REFERENCE TO RELATED APPLICATION [0001] This application is a divisional application of U.S. patent application Ser. No. 17/577,800, filed on Jan. 18, 2022, all of which are hereby expressly incorporated by reference into the present application.

BACKGROUND

[0002] As the gate pitch in a semiconductor device shrinks, the critical dimension (CD) of a contact shrinks as well. When the CD of the contact shrinks to a nanometer (nm) scale (for example, less than 30 nm), the resistivity of the contact increases rapidly due to surface scattering.

[0003] A via contact is electrically connected to a conductive contact (e.g., a metal silicide), which is disposed on an active region (e.g., a source/drain region), through a metal contact. The metal silicide is very sensitive to the environment in which manufacturing the semiconductor device is performed, and might be easily damaged during the manufacturing process of the semiconductor device, which may cause increase in the resistance thereof. In addition, when the interface between the via contact and the metal contact is too narrow, the interface resistance between the via contact and the metal contact cannot be reduced effectively. Therefore, a new metal contact structure and a new manufacturing method therefor are desirable to reduce the resistance between the via contact and the metal contact, and to protect the metal silicide from damage.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0004] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0005] FIG. 1 is a schematic view illustrating a semiconductor device in accordance with some embodiments.

[0006] FIG. 2 is a flow diagram illustrating a method for manufacturing a semiconductor device in accordance with some embodiments.

[0007] FIGS. 3 to 13 are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0008] FIGS. 14 to 17 are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0009] FIGS. 18 to 20 are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0010] FIGS. **21** to **23** are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0011] FIGS. **24** and **25** are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0012] FIGS. **26** and **27** are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0013] FIGS. **28** and **29** are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0014] FIG. **30** is a schematic view illustrating an intermediate stage of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0015] FIGS. **31** and **32** are schematic views illustrating intermediate stages of a method for manufacturing the semiconductor device in accordance with some embodiments.

[0016] FIG. **33** is a schematic view illustrating an intermediate stage of a method for manufacturing the semiconductor device in accordance with some embodiments.

DETAILED DESCRIPTION

[0017] The following disclosure provides many different embodiments, or examples, for implementing different features of the disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0018] Further, spatially relative terms, such as “on,” “over,” “above,” “below,” “proximate,” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0019] FIG. **1** illustrates a schematic view of an example of a semiconductor device **1** at an intermediate stage of a manufacturing method thereof in accordance with some embodiments. The semiconductor device **1** includes a semiconductor substrate **10**; source/drain (S/D) regions **11** (i.e., active regions) disposed in the semiconductor substrate **10**; a first interlayer dielectric (ILD) layer **12** disposed on the semiconductor substrate **10** and the S/D regions **11**; gate structures **13** which are inserted in the first ILD layer **12** and disposed on the semiconductor substrate **10**, and each of which is disposed between corresponding two of the S/D regions **11** and includes a gate dielectric **131** disposed on the semiconductor substrate **10** and a metal gate **132** disposed on the gate dielectric **131**; self-aligned contacts (SACs) **14** disposed on the gate structures **13**, respectively; inner gate spacers **15** disposed in the first ILD layer **12** to laterally cover the gate structures **13** and lower portions of the SACs **14**; outer gate spacers **16** disposed in the first ILD layer **12** to laterally cover the inner gate spacers **15**; conductive contacts **17** disposed on the S/D regions **11**, respectively; protective liners **18** disposed on the conductive contacts **17**, respectively; metal contacts **19** disposed on the protective liners **18**, respectively, and separated from the conductive contacts **17** by the protective liners **18**, respectively; and contact spacers **20** disposed in the first ILD layer **12** to laterally cover the conductive contacts **17** and the protective liners **18**. The semiconductor device **1** further includes a middle contact etch stop layer (MCESL) **21** disposed on

the first ILD layer **12** to cover the metal contacts **19**, the protective liners **18**, the contact spacers **20**, and the SACs **14**; a second ILD layer **22** disposed on the MCESL **21**; a first via contact **23** penetrating through the second ILD layer **22** and the MCESL **21** to be electrically connected to a corresponding one of the metal contacts **19**; a second via contact **24** penetrating through the second ILD layer **22**, the MCESL **21**, and a corresponding one of the SACs **14** to be electrically connected to a corresponding one of the gate structures **13**; an etch stop layer **25** disposed on the second ILD layer **22**; a dielectric layer **26** disposed on the etch stop layer **25**; and a metal line **27** disposed in the dielectric layer **26**, and electrically connected to a corresponding one of the metal contacts **19** through the first via contact **23** or electrically connected to a corresponding one of the gate structures **13** through the second via contact **24**.

[0020] In some embodiments, the semiconductor substrate **10** may include, for example, but not limited to, an elemental semiconductor or a compound semiconductor. The elemental semiconductor includes a single species of atoms, such as silicon (Si) or germanium (Ge) in column XIV of the periodic table, and may be in crystal, polycrystalline, or an amorphous structure. Other suitable materials are within the contemplated scope of the present disclosure. The compound semiconductor includes two or more elements, and examples thereof may include, but are not limited to, silicon carbide (SiC), gallium arsenide (GaAs), gallium phosphide (GaP), indium phosphide (InP), indium arsenide (InAs), indium antimonide (InSb), silicon germanium (SiGe), gallium arsenide phosphide (GaAsP), aluminum indium arsenide (AlInAs), aluminum gallium arsenide (AlGaAs), gallium indium arsenide (GaInAs), gallium indium phosphide (GaInP), and gallium indium arsenide phosphide (GaInAsP). Other suitable materials are within the contemplated scope of the present disclosure. The compound semiconductor may have a gradient feature in which the compositional ratio thereof changes from one location to another location in the compound semiconductor. The compound semiconductor may be formed over a silicon substrate. The compound semiconductor may be strained. In some embodiments, the semiconductor substrate **10** may include a multilayer compound semiconductor structure. In some embodiments, the semiconductor substrate **10** may be a semiconductor-on-insulator (SOI) (e.g., silicon germanium-on-insulator (SGOI)). Generally, an SOI substrate includes a layer of a semiconductor material such as epitaxial silicon, germanium, silicon germanium, or combinations thereof. Other suitable materials are within the contemplated scope of the present disclosure. The SOI substrate may be doped with a P-type dopant, for example, but not limited to, boron (Br), aluminum (Al), or gallium (Ga). Other suitable materials are within the contemplated scope of the present disclosure. Alternatively, the SOI substrate may be doped with an N-type dopant, for example, but not limited to, nitrogen (N), phosphorous (P), or arsenic (As). Other suitable materials are within the contemplated scope of the present disclosure.

[0021] In some embodiments, the S/D regions **11** may be formed by epitaxially growing a layer of a semiconductor material using a selective epitaxial growth (SEG) process. The S/D regions **11** may be, for example, but not limited to, crystalline silicon (or other suitable semiconductor materials) in-situ doped with a P-type impurity during the SEG process, so as to form P-type S/D regions for PMOS (P-type metal oxide semiconductor) transistors. The P-type impurity may be, for example, but not limited to, boron, aluminum, gallium, indium, BF.sub.2, other suitable materials, or combinations thereof. The S/D regions **11** may include one or multiple layers of the semiconductor material. In some embodiments, the S/D regions **11** may be fabricated by forming a SiGe alloy layer using the SEG process and then forming a Si cap layer on top of the SiGe alloy layer, followed by implanting a P-type light doping grain (for example, but not limited to, boron, aluminum, gallium, indium, BF.sub.2, other suitable materials, or combinations thereof) so as to form the P-type S/D regions. In some embodiments, the S/D regions **11** may be, for example, but not limited to, crystalline silicon (or other suitable semiconductor materials) in-situ doped with an N-type impurity during the SEG process, so as to form N-type S/D regions for NMOS (N-type metal oxide semiconductor) transistors. The N-type impurity may be, for example, but not limited

to, phosphorous, nitrogen, arsenic, antimony, other suitable materials, or combinations thereof. In some embodiments, the S/D regions **11** may be fabricated by forming a SiGe alloy layer using the SEG process and then forming a Si cap layer on top of the SiGe alloy layer, followed by implanting an N-type light doping grain (for example, but not limited to, phosphorous, nitrogen, arsenic, antimony, other suitable materials, or combinations thereof) so as to form the N-type S/D regions. [0022] In some embodiments, the first ILD layer **12** may include a dielectric material, such as silicon oxide, silicon nitride, silicon oxynitride, spin-on glass (SOG), amorphous fluorinated carbon, fluorinated silica glass (FSG), carbon doped silicon oxide (e.g., SiCOH), Black Diamond® (purchased from Applied Materials Inc., Santa Clara, Calif.), Xerogel, Aerogel, polyimide, Parylene, BCB (bis-benzocyclobutenes), Flare, SiLK™ (purchased from Dow Chemical Co., Midland, Mich.), non-porous materials, porous materials, or combinations thereof. In some embodiments, the first ILD layer **12** may include a high density plasma (HDP) dielectric material (e.g., HDP oxide), a high aspect ratio process (HARP) dielectric material (e.g., HARP oxide), or a combination thereof. In some embodiments, the first ILD layer **12** may be a planarized dielectric film. The first ILD layer **12** may be formed by a suitable deposition process known to those skilled in the art of semiconductor fabrication, for example, but not limited to, chemical vapor deposition (CVD), physical vapor deposition (PVD), atomic layer deposition (ALD), high density plasma CVD (HDPCVD), metal organic CVD (MOCVD), remote plasma CVD (RPCVD), plasma enhanced CVD (PECVD), or low-pressure chemical vapor deposition (LPCVD).

[0023] In some embodiments, the gate dielectric **131** may be a high-k dielectric layer. In some embodiments, the gate dielectric **131** may include hafnium oxide (HfO), hafnium silicon oxide (HfSiO), hafnium silicon oxynitride (HfSiON), hafnium tantalum oxide (HfTaO), hafnium titanium oxide (HfTiO), hafnium zirconium oxide (HfZrO), metal oxides, metal nitrides, metal silicates, metal oxynitrides, metal aluminates, transition metal nitrides, transition metal silicates, transition metal oxides, silicon oxide, silicon nitride, silicon oxynitride, zirconium silicate, zirconium aluminate, other suitable high-k dielectric materials, or combinations thereof. Examples of metal oxides for high-k dielectrics include oxides of Li, Be, Mg, Ca, Sr, Sc, Y, Zr, Hf, Al, La, Ce, Pr, Nd, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu, or mixtures thereof. An interfacial layer may be disposed below the gate dielectric **131** to reduce damage between the gate dielectric **131** and the semiconductor substrate **10**. The interfacial layer may comprise silicon oxide.

[0024] In some embodiments, the metal gate **132** may include several layers, for example, but not limited to, a blocking/wetting layer, a work function layer, and a conductive layer. The blocking/wetting layer prevents or reduces metal impurities from penetrating into any dielectric layers (for example, the gate dielectric **131**) disposed below the blocking/wetting layer, and also provides desirable interface quality between the blocking/wetting layer and any material layer formed over the blocking/wetting layer. In some embodiments, the blocking/wetting layer includes, for example, but not limited to, titanium aluminum nitride (TiAlN), other suitable metal nitrides, titanium aluminum carbonitride (TiAlCN), other suitable metal carbonitrides, or combinations thereof. The work function layer includes a material which is used to tune some work function values of the metal gate **132**. In some embodiments, the work function layer may include titanium aluminum carbonitride which has a composition different from that of the titanium aluminum carbonitride of the blocking/wetting layer. In some embodiments, the conductive layer includes aluminum, copper, tungsten, a metal alloy, a metal silicide, other conductive materials, or combinations thereof.

[0025] In some embodiments, the SACs **14** includes silicon nitride, silicon nitride doped with carbon, silicon oxide, silicon oxynitride, silicon oxynitride doped with carbon, amorphous carbon material, silicon carbide, other nitride materials, other carbide materials, aluminum oxide, other oxide materials, other metal oxides, boron nitride, boron carbide, and other low-k dielectric materials or low-k dielectric materials doped with one or more of carbon, nitrogen, and hydrogen, or other suitable materials.

[0026] In some embodiments, the inner gate spacers **15** may be formed from a spacer layer which may include, for example, but not limited to, silicon oxide, silicon nitride, silicon carbide, silicon oxycarbide, silicon oxynitride, silicon carbonitride, silicon oxycarbonitride, or combinations thereof. The outer gate spacers **16** may be formed from a spacer layer which may be similar to that for forming the inner gate spacers **15**.

[0027] In some embodiments, the conductive contacts **17** may include, for example, but are not limited to, a metal silicide material. Examples of the metal silicide material may include titanium silicide (Ti.sub.xSi.sub.y), molybdenum silicide (Mo.sub.xSi.sub.y), nickel silicide (Ni.sub.xSi.sub.y), ruthenium silicide (Ru.sub.xSi.sub.y), cobalt silicide (Co.sub.xSi.sub.y), tungsten silicide (W.sub.xSi.sub.y), europium silicide (Eu.sub.xSi.sub.y), erbium silicide (Er.sub.xSi.sub.y), titanium germanosilicide (Ti.sub.xSi.sub.yGe.sub.z), molybdenum germanosilicide (Mo.sub.xSi.sub.yGe.sub.z), nickel germanosilicide (Ni.sub.xSi.sub.yGe.sub.z), ruthenium germanosilicide (Ru.sub.xSi.sub.yGe.sub.z), cobalt germanosilicide (Co.sub.xSi.sub.yGe.sub.z), tungsten germanosilicide (W.sub.xSi.sub.yGe.sub.z), germanosilicide (Eu.sub.xSi.sub.yGe.sub.z), erbium germanosilicide (Er.sub.xSi.sub.yGe.sub.z), and the like, and combinations thereof, but are not limited thereto. The metal silicide material may be subjected to a nitridation treatment to reduce oxidation thereof during the manufacturing method of the semiconductor device **1**. For example, titanium silicide may be subjected to a nitridation treatment so as to form titanium silicon nitride (TiSiN), and nickel silicide may be subjected to a nitridation treatment so as to form nickel silicon nitride (NiSiN).

[0028] The protective liners **18** are used to protect the conductive contacts **17** from oxidation during the manufacturing method of the semiconductor device **1** (for example, in a front opening unified pod (FOUP)). In some embodiments, the protective liners **18** may include a metal material, examples of which include ruthenium (Ru), cobalt (Co), molybdenum (Mo), tungsten (W), nickel (Ni), iridium (Ir), rhodium (Rh), osmium (Os), and the like, and combinations thereof, but are not limited thereto, as well as nitrides of the metal material.

[0029] In some embodiments, the metal contacts **19** may include a metal material, examples of which include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof, but are not limited thereto. The metal material for the metal contacts **19** may be the same as that for the protective liners **18**.

[0030] In some embodiments, the contact spacers **20** may include, for example, but not limited to, silicon oxide, silicon nitride, silicon carbide, silicon oxycarbide, silicon oxynitride, silicon carbonitride, silicon oxycarbonitride, boron nitride, silicon boron nitride, or combinations thereof. The contact spacers **20** may have a thickness ranging from about 10 Å to about 50 Å. When the thickness of the contact spacers **20** is less than 10 Å, the protective liners **18** cannot be fully covered by the contact spacers **20**. When the thickness of the contact spacers **20** is greater than 50 Å, the resistance attributed by the contact spacers **20** may be increased undesirably.

[0031] The MCESL **21** may be formed on the first ILD layer **12** by a suitable deposition process known to those skilled in the art of semiconductor fabrication, for example, but not limited to, CVD, PVD, ALD, HDPCVD, MOCVD, RPCVD, PECVD, or LPCVD. In some embodiments, the MCESL **21** includes silicon nitride, silicon nitride doped with carbon, silicon oxide, silicon oxynitride, silicon oxynitride doped with carbon, amorphous carbon material, silicon carbide, other nitride materials, other carbide materials, aluminum oxide, other oxide materials, other metal oxides, boron nitride, boron carbide, and other low-k dielectric materials or low-k dielectric materials doped with one or more of carbon, nitrogen, and hydrogen, or other suitable materials.

[0032] The second ILD layer **22** is formed on the MCESL **21** by a suitable deposition process which may be the same or similar to that for forming the first ILD layer **12**. The second ILD layer **22** may include a dielectric material which may be the same or similar to that for forming the first ILD layer **12**.

[0033] The first via contact **23** is formed in the second ILD layer **22** and penetrates through the

MCESL **21** by, for example, but not limited to, a single damascene process, so as to be electrically connected to the corresponding one of the metal contacts **19**. In some embodiments, formation of the first via contact **23** includes the following steps. First, a via opening is formed through the second ILD layer **22** and MCESL **21** to expose the corresponding one of the metal contacts **19** from the via opening. After formation of the via opening, the first via contact **23** is formed by depositing a metal material to fill the via opening and then removing excess of the metal material above the second ILD **22** by a planarization technique, such as chemical mechanical planarization (CMP). In some embodiments, the metal material may include, for example, but not limited to, Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof. In some embodiments, deposition of the metal material may be conducted by a suitable technique known to those skilled in the art of semiconductor fabrication, for example, but not limited to, CVD, PECVD, ALD, PEALD, selective CVD, selective ALD, super conformal ALD, super conformal CVD, or other suitable deposition techniques. In some embodiments, a metal halide precursor (e.g., fluoride, chloride, bromide, or iodide of the metal material) or a metal organic precursor (including an organic ligand (e.g., —OC.sub.1-16, —CO, -acac, or the like) and the metal material) may be used for selective CVD or selective ALD.

[0034] The second via contact **24** is formed in the second ILD layer **22** and penetrates through the MCESL **21** and the corresponding one of the SACs **14** by, for example, but not limited to, a dual damascene process, so as to be electrically connected to the corresponding one of the gate structures **13**. In some embodiments, formation and material of the second via contact **24** may be the same as or similar to those of the first via contact **23**.

[0035] The etch stop layer **25** may be formed on the second ILD layer **22** by a suitable deposition process which may be the same as or similar to that for forming the MCESL **21**. The etch stop layer **25** may include a material which may be the same or similar to that for forming the MCESL **21**.

[0036] The dielectric layer **26** may be formed on the etch stop layer **25** by a suitable deposition process which may be the same as or similar to that for forming the first ILD layer **12**. The dielectric layer **26** may include a dielectric material which may be the same or similar to that for forming the first ILD layer **12**.

[0037] The metal line **27** may be formed in the dielectric layer **26** by a process which may be the same or similar to that for forming the first via contact **23**. In some embodiments, the metal line **27** may include a barrier layer **271**, a first liner layer **272** covering the barrier layer **271**, a second liner layer **273** covering the first liner layer **272**, and a conductive layer **274** filled in a space defined by the second liner layer **273**. In some embodiments, the barrier layer **271** may include titanium, tantalum, other suitable metals, titanium nitride, tantalum nitride, other suitable metal nitrides, and the like. The first liner layer **272** may include cobalt and other suitable metals. The second liner layer **273** may include ruthenium and other suitable metals. The conductive layer **274** may include silver, aluminum, copper, tungsten, nickel, other suitable metal materials, alloys thereof, or combinations thereof.

[0038] The interface between the first via contact **23** and the corresponding one of the metal contacts **19** has a relatively small contact area, which contributes to a relatively large interface resistance between the first via contact **23** and the corresponding one of the metal contacts **19**, resulting in the semiconductor device **1** may have a relatively high resistance.

[0039] FIG. **2** is a flow diagram illustrating a method **100** for manufacturing a semiconductor device in accordance with some embodiments. FIGS. **3** to **13** illustrate schematic views of a semiconductor device **2** during various stages of the method **100** shown in FIG. **2**. The method **100** and the semiconductor device **2** are collectively described below. However, additional steps can be provided before, after or during the various stages of the method **100**, and some of the steps described herein may be replaced by other steps or be eliminated. Similarly, further additional features may be present in the semiconductor device **2**, and/or the features present may be replaced or eliminated in additional embodiments.

[0040] Referring to FIG. 2, the method **100** begins at block **101**, where conductive contacts are formed. Referring to the example illustrated in FIG. 3, the semiconductor device **2** includes the semiconductor substrate **10**; the source/drain (S/D) regions **11** (i.e., the active regions) disposed in the semiconductor substrate **10**; the first ILD layer **12** disposed on the semiconductor substrate **10** and the S/D regions **11**; the gate structures **13** which are inserted in the first ILD layer **12** and disposed on the semiconductor substrate **10**, and each of which is disposed between corresponding two of the S/D regions **11**; the SACs **14** disposed on the gate structures **13**, respectively; the inner gate spacers **15** disposed in the first ILD layer **12** to laterally cover the gate structures **13** and lower portions of the SACs **14**; the outer gate spacers **16** disposed in the first ILD layer **12** to laterally cover the inner gate spacers **15**; and the contact spacers **20** disposed in the first ILD layer **12** to laterally cover the outer spacers **16** and the SACs **14**. The semiconductor substrate **10**, the source/drain (S/D) regions **11**, the first ILD layer **12**, the gate structures **13**, the SACs **14**, the inner gate spacers **15**, the outer gate spacers **16**, and the contact spacers **20** are the same as or similar to those described above for the semiconductor device **1** with reference to FIG. 1, and thus details thereof are omitted for the sake of brevity.

[0041] Referring to the examples illustrated in FIGS. 3 and 4, the conductive contacts **17** may be formed on the S/D regions **11**, respectively, by a suitable formation process known to those skilled in the art of semiconductor fabrication. For example, in some embodiments in which the conductive contacts **17** are made of metal silicide, the conductive contacts **17** may be formed by a pre-silicidation implantation process in which implant regions are formed, followed by a silicidation process in which the implant regions are subjected to a silicidation process so as to form the conductive contacts **17**. In the pre-silicidation implantation process, dopants (for example, but not limited to, metal dopants) are implanted through trenches **121** defined by the contact spacers **20**. In some embodiments, the silicidation process may include an annealing operation, the conductive contacts **17** made of metal silicide are formed only in the implant regions including the metal dopants, and the conductive contacts **17** made of metal silicide are formed after the annealing operation. The conductive contacts **17** may have a thickness of at least about 3 nm. When the thickness of the conductive contacts **17** is less than 3 nm, the conductive contacts **17** may not be formed as a complete layered structure on the S/D regions **11**. In some embodiments, the thickness of the conductive contacts **17** ranges from about 3 nm to about 10 nm. Details of the material for the conductive contacts **17** are as described above for the semiconductor device **1** with reference to FIG. 1, and thus are omitted for the sake of brevity.

[0042] Referring to FIG. 2, the method **100** then proceeds to block **102**, where protective liners are formed. Referring to the example illustrated in FIG. 5, a protective layer **18'** is conformally deposited to cover first ILD layer **12**, the SACs **14**, the contact spacers **20**, and the conductive contacts **17**. In some embodiments, the protective layer **18'** may be formed by a suitable in-situ deposition process known to those skilled in the art of semiconductor fabrication, for example, but not limited to, CVD, PECVD, ALD, PEALD, or other suitable deposition techniques. In some embodiments, the protective layer **18'** may include a metal material, examples of which include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof, and but are not limited thereto. In order to prevent the conductive contacts **17** from being damaged during the in-situ deposition process, the in-situ deposition process is performed in an oxygen-free environment (for example, an environment in which H₂O, CO₂, CO, O, OH, and the like are not included), which includes the precursors for forming the protective layer **18'** with the exception of halide such as chloride and fluoride, and which includes the carrier gas for carrying the precursors with the exception of carbon dioxide, carbon monoxide, oxygen, and the like. The chamber for deposition of the metal material of the protective layer **18'** is positioned proximate to that for forming the conductive contacts **17**.

[0043] Referring to the example illustrated in FIG. 6, a bottom anti-reflective coating (BARC) layer **28** (i.e., a photoresist layer, for example, but not limited to, a silicon oxynitride (SiON) layer)

is deposited by a suitable coating process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a spin-coating process) so as to fill the trenches **121**, and is then etched back to a height less than a depth of the trenches **121** by a suitable etching process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a dry etching process).

[0044] Referring to the examples illustrated in FIGS. **6** and **7**, a portion of the protective layer **18'** above the BARC layer **28** is removed by a suitable etching process (for example, but not limited to, a wet etching process) based on a relatively high etching selectivity of the protective layer **18'** with respect to the BARC layer **28**. The BARC layer **28** is then removed completely by, for example, but not limited to, a dry etching process to form the protective liners **18**. Each of the protective liners **18** includes a bottom portion and a sidewall portion extending upwardly from a periphery of the bottom portion. In some embodiments, the protective liners **18** may have a thickness ranging from about 0.3 nm to about 5.0 nm. When the thickness of the protective liners **18** is less than 0.3 nm, the conductive contacts **17** may not be protected effectively by the protective liners **18** during the subsequent stages of the manufacturing method of the semiconductor device **2**. When the thickness of the protective liners **18** is greater than 5.0 nm, the resistance attributed by the protective liners **18** may be increased undesirably.

[0045] Referring to FIG. **2**, the method **100** then proceeds to block **103**, where lower metal contacts are formed. Referring to the examples illustrated in FIGS. **7** and **8**, a first metal material **M1** is filled into the trenches **121** by a selective deposition process (for example, but not limited to, selective CVD or selective ALD), a super conformal deposition process (for example, but not limited to, super conformal ALD or super conformal CVD), or the like. The super conformal deposition process is a conformal deposition process in which a deposition rate of the first metal material **M1** on the bottom portions of the protective liners **18** is greater than that on the sidewall portions of the protective liners **18**. Since the selective deposition process or the super conformal deposition process is used and the protective liners **18** have a height less than the depth of the trenches **121**, no seam is formed in the first metal material **M1** filled into the trenches **121**.

Examples of the first metal material **M1** include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof, and but are not limited thereto. In some embodiments, a metal halide precursor (e.g., fluoride, chloride, bromide, or iodide of the metal material) or a metal organic precursor (including an organic ligand (e.g., —OC.sub.1-16, —CO, -acac, or the like) and the metal material) may be used for the selective deposition process or the super conformal deposition process. When the metal organic precursor is used, impurities such as carbon (C), nitrogen (N), oxygen (O), or combinations thereof may be included in an amount ranging from about 0.001% to about 2% in the first metal material **M1** filled into the trenches **121**. An adhesion layer **29** (for example, but not limited to, metals, oxides, nitrides, and the like) is conformally deposited to cover the first ILD **12**, the SACs **14**, and the first metal material **M1** so as to prevent the first metal material **M1** from damage such as being stripped from the contacts spacers **20** and/or the sidewall portions of the protective liners **18** in the subsequent process (for example, CMP). A dielectric layer **30** (for example, but not limited to, silicon oxide, silicon nitride, silicon oxynitride, or combinations thereof) is deposited on the adhesion layer **29**. A planarization technique such as CMP is then performed to remove the dielectric layer **30**, the adhesion layer **29** and excess of the first metal material **M1** above the first ILD layer **12**, and the first metal material **M1** remaining in the trenches **121** is etched back by a suitable etching process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a dry etching process) so as to form the lower metal contacts **191**, which have a height less than the depth of the trenches **121**. The conductive contacts **17** are separated from the lower metal contacts **191** by the protective liners **18**, respectively. The bottom portions of the protective liners **18** are disposed between the conductive contacts **17** and the lower metal contacts **191**, respectively. In some embodiments, the lower metal contacts **191** may be formed directly on the protective liners **18** by controlling the time period of

the selective deposition process, the super conformal deposition process, or the like.

[0046] Referring to FIG. 2, the method **100** then proceeds to block **104**, where upper metal contacts are formed. Referring to the examples illustrated in FIGS. 9, 10 and 11, a second metal material M2 is filled into the trenches **121** by a suitable deposition process known to those skilled in the art of semiconductor fabrication, for example, but not limited to, PVD, sputtering, selective CVD, CVD, selective ALD, ALD, or the like. Examples of the second metal material M2 include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof, and but are not limited thereto. A planarization technique such as CMP or etching back is then performed to remove excess of the second metal material M2 above the first ILD layer **12** so as to form the upper metal contacts **192**. The second metal material M2 for forming the upper metal contacts **192** should be different from the first metal material M1 for forming the lower metal contacts **191**. The upper metal contacts **192** are in contact with and cooperate with the lower metal contacts **191**, respectively, to form hybrid metal contact structures **19'**. Each of the upper metal contacts **192** has a bottom surface with a dimension which is the same as a dimension of a top surface of a corresponding one of the lower metal contacts **191**.

[0047] Referring to FIG. 2, the method **100** then proceeds to block **105**, where a first via contact is formed, and block **106**, where a second via contact is formed. Referring the example illustrated in FIG. 12, the MCESL **21** is formed on the first ILD layer **12**. The formation and the material of the MCESL **21** are the same as or similar to those of the MCESL **21** described above for the semiconductor device **1** with reference to FIG. 1, and thus details thereof are omitted for the sake of brevity. The second ILD layer **22** is formed on the MCESL **21**. The formation and the material of the second ILD layer **22** are the same as or similar to those of the second ILD layer **22** described above for the semiconductor device **1** with reference to FIG. 1, and thus details thereof are omitted for the sake of brevity.

[0048] The first via contact **23** is formed in the second ILD layer **22** and penetrates through the MCESL **21** so as to be electrically connected to the upper metal contact **192** of a corresponding one of the hybrid metal contact structures **19'**. The first via contact **23** has a horizontal cross-section area less than a contact area between the upper metal contacts **192** and the lower metal contacts **191**. In some embodiments, formation of the first via contact **23** includes the following steps. First, a via opening is formed through the second ILD layer **22** and MCESL **21** to expose the upper metal contact **192** of the corresponding one of the hybrid metal contact structures **19'** from the via opening. After formation of the via opening, the first via contact **23** is formed by depositing a metal material to fill the via opening and then removing excess of the metal material by a planarization technique, such as CMP. In some embodiments, the metal material may include, for example, but not limited to, Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, or combinations thereof. The metal material for forming the first via contact **23** should be the same as that for forming the upper metal contacts **192**. In some embodiments, deposition of the metal material for forming the first via contact **23** may be conducted by a suitable technique known to those skilled in the art of semiconductor fabrication, for example, but not limited to, CVD, PECVD, ALD, PEALD, selective CVD, selective ALD, super conformal ALD, super conformal CVD, or other suitable deposition techniques. In some embodiments, a metal halide precursor (e.g., fluoride, chloride, bromide, or iodide of the metal material) or a metal organic precursor (including an organic ligand (e.g., —OC.sub.1-16, —CO, -acac, or the like) and the metal material) may be used for the selective CVD or the selective ALD. When the metal organic precursor is used, impurities such as carbon (C), nitrogen (N), oxygen (O), or combinations thereof may be included in the first via contact **23** in an amount ranging from 0.001% to 2%.

[0049] The second via contact **24** is formed in the second ILD layer **22** and penetrates through the MCESL **21** and a corresponding one of the SACs **14** to be electrically connected to a corresponding one of the gate structures **13**. In some embodiments, formation and material of the second via contact **24** may be the same as or similar to those of the first via contact **23**. In some embodiments,

the second via contact **24** may be configured as a single layer structure including two different metal materials. In some embodiments, the second via contact **24** may be configured as a two layered structure, in which one layer includes a metal material different from the metal material of the other layer. The second via contact **24** may be formed with or without seam therein. The first via contact **23** and the second via contact **24** may be formed simultaneously or separately.

[0050] Referring to FIG. 2, the method **100** then proceeds to block **107**, where a metal line is formed. Referring the example illustrated in FIG. 13, the etch stop layer **25** is formed on the second ILD layer **22**, the dielectric layer **26** is formed on the etch stop layer **25**, and the metal line **27** is formed in the dielectric layer **26** to be electrically connected to the upper metal contact **192** of the corresponding one of the hybrid metal contact structures **19'** through the first via contact **23** or electrically connected to a corresponding one of the gate structures **13** through the second via contact **24**. Details of the formations and the materials of the etch stop layer **25**, the dielectric layer **26**, the metal line **27** are described above for the semiconductor device **1** with reference to FIG. 1, and thus are omitted for the sake of brevity

[0051] In some embodiments, formation of the lower metal contacts **191** and formation of the protective liners **18** are performed simultaneously. Referring to the examples illustrated in FIGS. 5 and 14, the first metal material **M1** is deposited on the protective layer **18'** and filled into the trenches **121** by a deposition process (for example, but not limited to, CVD, PECVD, ALD, PEALD, or the like) other than the selective deposition process or the super conformal deposition process. Examples of the first metal material **M1** include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, and combinations thereof, but are not limited thereto. The first metal material **M1** for forming the lower metal contacts **191** is the same as the metal material for forming the protective liners **18**. Since a deposition process other than the selective deposition process or the super conformal deposition process is used for depositing the first metal material **M1**, seams(S) may be formed in the first metal material **M1** filled in the trenches **121**. The heights of the seams (S) will be increased with an increase of the CD of the lower metal contacts **191** to be formed. Referring to the examples illustrated in FIGS. 14 and 15, a planarization technique such as CMP is then performed to remove excess of the first metal material **M1** and top portions of the protective layer **18'** above the first ILD layer **12**. Referring to the examples illustrated in FIGS. 15 and 16, the first metal material **M1** and the protective layer **18'** remaining in the trenches **121** are etched back by a suitable etching process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a dry etching process) to form the protective liners **18** and the lower metal contacts **191** simultaneously. The seams(S) may be formed in the lower metal contacts **191**. Since the first metal material **M1** for forming the lower metal contacts **191** is the same as the metal material for forming the protective liners **18**, the top surfaces of the lower metal contacts **191** and the top surfaces of the sidewall portions of the protective liners **18** are flush with each other due to no difference in the etching selectivity between the first metal material **M1** for forming the lower metal contacts **191** and the metal material for forming the protective liners **18**. Therefore, in the semiconductor device **2** formed at the stage illustrated in FIG. 17, each of the hybrid metal contact structures **19'** includes the lower metal contact **191** which may be formed with the seam(S), and the upper metal contact **192** which is disposed on the lower metal contact **191** and the protective liner **18**.

[0052] In some embodiments, formation of the lower metal contacts **191** and formation of the protective liners **18** are performed simultaneously. Referring to the examples illustrated in FIGS. 5 and 18, the first metal material **M1** is deposited on the protective layer **18'** and filled into the trenches **121** by the super conformal deposition process (for example, but not limited to, super conformal ALD or super conformal CVD). The protective layer **18'** includes a metal material, for example, but not limited to, Ru, Co, Mo, W, Ni, Ir, Rh, Os, or the like, or combinations thereof, or nitrides of the metal material. Examples of the first metal material **M1** include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, and combinations thereof, but are not limited thereto. The first metal material **M1** for forming the lower metal contacts **191** is different from the metal material for

forming the protective liners **18**, and has a relatively high etching selectivity with respect to the metal material for forming the protective liners **18**. Since the super conformal deposition process is used for depositing the first metal material **M1**, the first metal material **M1** filled in the trenches **121** is not formed with seams. Referring to the examples illustrated in FIGS. **18** and **19**, a planarization technique such as CMP is then performed to remove excess of the first metal material **M1** and top portions of the protective layer **18'** above the first ILD layer **12**. The first metal material **M1** remaining in the trenches **121** is then selectively etched back by a suitable etching process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a dry etching process) based on the relatively high etching selectivity of the first metal material **M1** with respect to the metal material for forming the protective liners **18**, so as to form the protective liners **18** and the lower metal contacts **191**. The top surfaces of the lower metal contacts **191** are lower than those of the sidewall portions of the protective liners **18**. Therefore, in the semiconductor device **2** formed at the stage illustrated in FIG. **20**, each of the hybrid metal contact structures **19'** includes the lower metal contact **191** which is not formed with the seam therein, and the upper metal contact **192** which is disposed on the lower metal contact **191**. The upper and lower metal contacts **192** and **191** of each of the hybrid metal contact structures **19'** are laterally covered by the sidewall portion of a corresponding one of the protective liners **18**.

[0053] In some embodiments, formation of the lower metal contacts **191** and formation of the protective liners **18** are performed simultaneously. Referring to the examples illustrated in FIGS. **5** and **21**, the first metal material **M1** is deposited on the protective layer **18'** and filled into the trenches **121** by a deposition process (for example, but not limited to, CVD, PECVD, ALD, PEALD, or the like) other than the selective deposition process or the super conformal deposition process. The protective layer **18'** includes a metal material, for example, but not limited to, Ru, Co, Mo, W, Ni, Ir, Rh, Os, or the like, or combinations thereof, or nitrides of the metal material. Examples of the first metal material **M1** include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, and combinations thereof, but are not limited thereto. The first metal material **M1** for forming the lower metal contacts **191** is different from the metal material for forming the protective liners **18**, and has a relatively high etching selectivity with respect to the metal material for forming the protective liners **18**. Since a deposition process other than the selective deposition process or the super conformal deposition process is used for depositing the first metal material **M1**, the seams(S) may be formed in the first metal material **M1** filled in the trenches **121**. Referring to the examples illustrated in FIGS. **21** and **22**, a planarization technique such as CMP is then performed to remove excess of the first metal material **M1** and top portions of the protective layer **18'** above the first ILD layer **12**. The first metal material **M1** remaining in the trenches **121** is then selectively etched back by a suitable etching process known to those skilled in the art of semiconductor fabrication (for example, but not limited to, a dry etching process) based on the relatively high etching selectivity of the first metal material **M1** with respect to the metal material for forming the protective liners **18**, so as to form the protective liners **18** and the lower metal contacts **191**. The top surfaces of the lower metal contacts **191** are lower than those of the sidewall portions of the protective liners **18**, and the seams(S) may be formed in the lower metal contacts **191**. Therefore, in the semiconductor device **2** formed at the stage illustrated in FIG. **23**, each of the hybrid metal contact structures **19'** includes the lower metal contact **191** which may be formed with the seam(S) therein, and the upper metal contact **192** which is disposed on the lower metal contact **191**. The upper and lower metal contacts **192**, **191** of each of the hybrid metal contact structures **19'** are laterally covered by the sidewall portion of a corresponding one of the protective liners **18**.

[0054] In some embodiments, the lower metal contacts **191** are formed directly on the protective liners **18** by a selective deposition process. Referring to the examples illustrated in FIGS. **7** and **24**, after the protective liners **18** are formed, the lower metal contacts **191** having a height less than the depth of the trenches **121** are directly formed on the protective liners **18** by depositing the first metal material **M1** on the protective liners **18** using the selective deposition process (for example,

but not limited to, selective CVD or selective ALD) for a controlled time period. Examples of the first metal material **M1** include Ru, Co, Mo, W, Ni, Ir, Rh, Os, and the like, and combinations thereof, but are not limited thereto. The seams(**S**) may be formed in the lower metal contacts **191**. Therefore, in the semiconductor device **2** formed at the stage illustrated in FIG. **25**, each of the hybrid metal contact structures **19'** includes the lower metal contact **191** which is formed with the seam(**S**) therein, and the upper metal contact **192** which is disposed on the lower metal contact **191** and the protective liner **18**. The lower metal contact **191** of each of the hybrid metal contact structures **19'** is laterally covered by the sidewall portion of a corresponding one of the protective liners **18**.

[0055] In some embodiments, the protective liners **18** may be formed directly on the conductive contacts **17** by a selective deposition process. Referring to the examples illustrated in FIGS. **4** and **26**, after the conductive contacts **17** are formed, the protective liners **18** are directly formed on the conductive contacts **17** by the selective deposition process (for example, but not limited to, selective CVD or selective ALD). In some embodiments, nucleation sides may be formed on the contact spacers **20** due to loss of selectivity during the selective deposition process. In some embodiments, the protective liners **18** may have a thickness ranging from about 0.5 nm to about 10.0 nm. When the thickness of the protective liners **18** is less than 0.5 nm, the conductive contacts **17** may not be protected effectively by the protective liners **18** during the subsequent stages of the manufacturing method of the semiconductor device **2**. When the thickness of the protective liners **18** is greater than 10.0 nm, the resistance attributed by the protective liners **18** may be increased undesirably. In the semiconductor device **2** formed at the stage illustrated in FIG. **27**, each of the protective liners **18** is configured as a flat layer disposed on a corresponding one of the conductive contacts **17**, and each of the hybrid metal contact structures **19'** includes the lower metal contact **191** disposed on a corresponding one of the protective liners **18** and the upper metal contact **192** disposed on the lower metal contact **191**.

[0056] In some embodiments, the protective liners **18** and the lower metal contacts **191** may be formed separately by different selective etching back processes using different etchants. Referring to the example illustrated in FIG. **28**, after the excess of the first metal material **M1** and the top portions of the protective layer **18'** above the first ILD layer **12** are removed by the planarization technique such as CMP, the protective liners **18** are formed by selectively etching back the protective layers **18'** remaining in the trenches **121** using a first etchant based on a relatively high etching selectivity of the protective layer **18'** with respect to the first metal material **M1**. The lower metal contacts **191** are formed by selectively etching back the first metal material **M1** remaining in the trenches **121** using a second etchant based on a relatively high etching selectivity of the first metal material **M1** with respect to the protective layer **18'**. For example, when the protective layer **18'** is made of titanium nitride and the first metal material **M1** is ruthenium, the protective liners **18** may be formed by selectively etching back the protective layers **18'** remaining in the trenches **121** using chlorine gas as the first etchant, and the lower metal contacts **191** may be formed by selectively etching back the first metal material **M1** remaining in the trenches **121** using oxygen gas as the second etchant. The protective liners **18** may be formed before or after the lower metal contacts **191** are formed. The top surfaces of the sidewall portions of the protective liners **18** are lower than a top surface of the first ILD layer **12**, and higher than top surfaces of the lower metal contacts **191**. Therefore, in each of the hybrid metal contact structures **19'** in the semiconductor device **2** formed at the stage illustrated in FIG. **29**, the lower metal contact **191** is disposed on a corresponding one of the protective liners **18** and is laterally covered by the sidewall portion of the corresponding one of the protective liners **18**, and the upper metal contact **192** is disposed on the lower metal contact **191** and a lower portion of the upper metal contact **192** is laterally covered by the sidewall portion of the corresponding one of the protective liners **18**. In addition, the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at the stage illustrated in FIG. **29** have a height lower than that of the sidewall portions of the protective liners **18** in the

semiconductor device **2** formed at the stage illustrated in FIG. **20**, in which the protective liners **18** are formed without selectively etching back of the protective layers **18'** remaining in the trenches **121**. Similarly, referring to the example illustrated in FIG. **30**, the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at this stage, in which the protective liners **18** and the lower metal contacts **191** are formed separately by different selective etching back processes using different etchants, have a height lower than that of the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at the stage illustrated in FIG. **23**, in which the protective liners **18** are formed without selectively etching back of the protective layers **18'** remaining in the trenches **121**.

[0057] Referring to the example illustrated in FIG. **31**, in some alternative embodiments, after the protective liners **18** and the lower metal contacts **191** are formed separately by different selective etching back processes using different etchants, the top surfaces of the sidewall portions of the protective liners **18** are lower than the top surfaces of the lower metal contacts **191**, and the top surfaces of the lower metal contacts **191** are lower than the top surface of the first ILD layer **12**. Therefore, in each of the hybrid metal contact structures **19'** in the semiconductor device **2** formed at the stage illustrated in FIG. **32**, the lower metal contact **191** is disposed on a corresponding one of the protective liners **18** and a top portion thereof protrudes upwardly out of the sidewall portion of the corresponding one of the protective liners **18**, and the upper metal contact **192** is disposed on the lower metal contact **191** and a lower portion thereof laterally covers the top portion of lower metal contact **191**. In addition, the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at the stage illustrated in FIG. **32** have a height lower than that of the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at the stage illustrated in FIG. **20**, in which the protective liners **18** are formed without selectively etching back of the protective layers **18'** remaining in the trenches **121**. Similarly, referring to the example illustrated in FIG. **33**, the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at this stage, in which the protective liners **18** and the lower metal contacts **191** are formed separately by different selective etching back processes using different etchants, have a height lower than that of the sidewall portions of the protective liners **18** in the semiconductor device **2** formed at the stage illustrated in FIG. **23**, in which the protective liners **18** are formed without selectively etching back of the protective layers **18'** remaining in the trenches **121**.

[0058] Compared with the semiconductor device **1** illustrated in FIG. **1**, in which the metal material for forming the first via contact **23** is different from that for forming the metal contacts **19**, the metal material for forming the first via contact **23** in the semiconductor device **2** illustrated in FIGS. **13**, **17**, **20**, **23**, **25**, **27**, **29**, **30**, **32**, and **33** is the same as that for forming the upper metal contacts **192**, therefore, there is no interface resistance between the first via contact **23** and a corresponding one of the upper metal contacts **192**. In addition, compared with the interface between the first via contact **23** and the corresponding one of the metal contacts **19** in the semiconductor device **1**, the interface between the upper metal contact **192** and the lower metal contact **191** in the semiconductor device **2** has a relatively large contact area, and thus, the interface resistance between the upper metal contact **192** and the lower metal contact **191** of a corresponding one of the hybrid metal contact structures **19'** that is electrically connected to the first via contact **23** may be reduced compared to that between the first via contact **23** and the corresponding one of the metal contacts **19** in the semiconductor device **1**. Furthermore, since the conductive contacts **17** are protected by the protective liners **18**, they can be prevented from being damaged during the manufacturing method of the semiconductor device **2**, thereby avoiding increase in the resistance of the semiconductor device **2** thus manufactured.

[0059] In accordance with some embodiments of the present disclosure, a method for manufacturing a semiconductor device includes: forming a lower metal contact in a trench of a first dielectric structure disposed on a substrate, the lower metal contact having a height less than a depth of the trench and being made of a first metal material; forming an upper metal contact to fill

the trench and to be in contact with the lower metal contact, the upper metal contact being formed of a second metal material different from the first metal material and having a bottom surface with a dimension which is the same as a dimension of a top surface of the lower metal contact; forming a second dielectric structure on the first dielectric structure; and forming a via contact penetrating through the second dielectric structure to be electrically connected to the upper metal contact, the via contact being formed of a metal material which is the same as the second metal material.

[0060] In accordance with some embodiments of the present disclosure, the method for manufacturing the semiconductor device further includes, prior to forming the lower metal contact, forming a conductive contact on an active region in the substrate; and forming a protective liner on the conductive contact to separate the conductive contact from the lower metal contact.

[0061] In accordance with some embodiments of the present disclosure, formation of the protective liner includes: conformally depositing a protective layer on the first dielectric structure to cover the conductive contact; depositing a photoresist layer on the protective layer; etching back the photoresist layer to permit the photoresist layer to have a height less than the depth of the trench; after etching back the photoresist layer, removing a portion of the protective layer above the photoresist layer; and removing the photoresist layer.

[0062] In accordance with some embodiments of the present disclosure, formation of the lower metal contact is performed after forming the protective liner, and includes: selectively depositing the first metal material on the protective liner to fill the trench; and removing a top portion of the first metal material to permit the height of the lower metal contact to be less than the depth of the trench.

[0063] In accordance with some embodiments of the present disclosure, formation of the lower metal contact is performed after forming the protective liner, and includes selectively depositing the first metal material on the protective liner to directly form the lower metal contact having a height less than the depth of the trench.

[0064] In accordance with some embodiments of the present disclosure, formation of the lower metal contact and formation of the protective liner are performed simultaneously, and include: conformally depositing a protective layer on the first dielectric structure to cover the conductive contact; depositing the first metal material to fill the trench and to cover the protective layer; removing a portion of the first metal material and a portion of the protective layer above the first dielectric structure; and after removing the portion of the protective layer and the portion of the first metal material, etching back the first metal material in the trench.

[0065] In accordance with some embodiments of the present disclosure, formation of the protective liner includes selectively depositing a protective layer merely on the conductive contact.

[0066] In accordance with some embodiments of the present disclosure, formation of the lower metal contact is performed after forming the protective liner, and includes: depositing the first metal material to fill the trench and to cover the first dielectric structure and the protective liner; removing a portion of the first metal material above the first dielectric structure; and after removing the portion of the first metal material, etching back the first metal material in the trench.

[0067] In accordance with some embodiments of the present disclosure, formation of the upper metal contact includes depositing the second metal material on the lower metal contact to fill the trench and to cover the first dielectric structure; and removing a portion of the second metal material above the first dielectric structure.

[0068] In accordance with some embodiments of the present disclosure, a semiconductor device includes a first dielectric structure, a lower metal contact, an upper metal contact, a second dielectric structure, and a via contact. The lower metal contact is disposed in the first dielectric structure, has a height less than a height of the first dielectric structure, and is formed of a first metal material. The upper metal contact is disposed on and in contact with the lower metal contact in the first dielectric structure. The upper metal contact is formed of a second metal material different from the first metal material, and has a bottom surface with a dimension which is the same

as a dimension of a top surface of the lower metal contact. The second dielectric structure is disposed on the first dielectric structure. The via contact penetrates through the second dielectric structure to be electrically connected to the upper metal contact, and is formed of a metal material which is the same as the second metal material.

[0069] In accordance with some embodiments of the present disclosure, the semiconductor device further includes a substrate including an active region, a conductive contact disposed on the active region, and a protective liner disposed on the conductive contact to separate the conductive contact from the lower metal contact.

[0070] In accordance with some embodiments of the present disclosure, the protective liner is formed of a metal material which is the same as the first metal material.

[0071] In accordance with some embodiments of the present disclosure, the protective liner is formed of a metal-containing material different from the first metal material.

[0072] In accordance with some embodiments of the present disclosure, the protective liner includes a bottom portion disposed between the conductive contact and the lower metal contact, and a sidewall portion extending upwardly from a periphery of the bottom portion to laterally cover the lower metal contact.

[0073] In accordance with some embodiments of the present disclosure, the sidewall portion of the protective liner has a height which is the same as a height of the lower metal contact.

[0074] In accordance with some embodiments of the present disclosure, the sidewall portion of the protective liner has a height greater than a height of the lower metal contact so as to laterally cover the upper metal contact.

[0075] In accordance with some embodiments of the present disclosure, the sidewall portion of the protective liner has a height less than a height of the lower metal contact so as to permit a lower portion of the upper metal contact to laterally cover an upper portion of the lower metal contact.

[0076] In accordance with some embodiments of the present disclosure, the protective liner is configured as a flat layer.

[0077] In accordance with some embodiments of the present disclosure, a semiconductor device includes a first dielectric structure, a hybrid metal contact structure disposed in the first dielectric structure, a second dielectric structure disposed on the first dielectric structure, and a via contact. The hybrid metal contact structure includes a lower metal contact and an upper metal contact. The lower metal contact has a height less than a height of the first dielectric structure, and is formed of a first metal material. The upper metal contact is disposed on and in contact with the lower metal contact. The upper metal contact is formed of a second metal material different from the first metal material, and has a bottom surface with a dimension which is the same as a dimension of a top surface of the lower metal contact. The via contact penetrates through the second dielectric structure to be electrically connected to the upper metal contact. The via contact is formed of a metal material which is the same as the second metal material, and has a horizontal cross-section area that is less than a contact area between the upper metal contact and the lower metal contact.

[0078] In accordance with some embodiments of the present disclosure, the semiconductor device further includes a substrate including an active region, a conductive contact disposed on the active region, and a protective liner disposed on the conductive contact to separate the conductive contact from the hybrid metal contact structure.

[0079] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes or structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor device, comprising: a first dielectric layer; a lower metal contact disposed in the first dielectric layer, having a height less than a height of the first dielectric layer, and including a first metal material; an upper metal contact disposed in the first dielectric layer, the upper metal contact being located on and in contact with the lower metal contact, and including of a second metal material different from the first metal material; a contact spacer disposed in the first dielectric layer and laterally covering the lower metal contact and the upper metal contact; a second dielectric layer disposed on the first dielectric layer; and a via contact penetrating the second dielectric layer and connected to the upper metal contact, the via contact including a metal material which is the same as the second metal material.
2. The semiconductor device according to claim 1, wherein a contact area between the lower metal contact and the upper metal contact is greater than a contact area between the via contact and the upper metal contact.
3. The semiconductor device according to claim 1, further comprising: a substrate including an active region; a conductive contact disposed on the active region; and a protective liner disposed on the conductive contact to separate the conductive contact from the lower metal contact.
4. The semiconductor device according to claim 3, wherein the protective liner includes a metal material which is the same as the first metal material.
5. The semiconductor device according to claim 3, wherein the protective liner includes a metal-containing material different from the first metal material.
6. The semiconductor device according to claim 3, wherein the protective liner includes: a bottom portion disposed between the conductive contact and the lower metal contact, and a sidewall portion extending upwardly from a periphery of the bottom portion to laterally cover the lower metal contact.
7. The semiconductor device according to claim 6, wherein the sidewall portion of the protective liner has a height less than a height of the lower metal contact.
8. The semiconductor device according to claim 7, wherein the lower metal contact includes a first contact portion laterally covered by the sidewall portion of the protective liner, and a second contact portion disposed on the first contact portion and the sidewall portion of the protective liner.
9. The semiconductor device according to claim 7, wherein the upper metal contact includes a first contact portion disposed on the lower metal contact, and a second contact portion disposed between the first contact portion and the sidewall portion of the protective liner and laterally covering the lower metal contact.
10. The semiconductor device according to claim 6, wherein the sidewall portion of the protective liner has a height which is the same as a height of the lower metal contact.
11. The semiconductor device according to claim 6, wherein the sidewall portion of the protective liner has a height greater than a height of the lower metal contact.
12. The semiconductor device according to claim 11, wherein sidewall portion of the protective liner fully laterally covers the upper metal contact.
13. The semiconductor device according to claim 11, wherein the upper metal contact includes a first contact portion laterally covered by the sidewall portion of the protective liner, and a second contact portion disposed on the first contact portion and the sidewall portion of the protective liner.
14. The semiconductor device according to claim 3, wherein the protective liner is configured as a flat layer.
15. A semiconductor device, comprising: a first dielectric layer; a hybrid metal contact structure disposed in the first dielectric layer, and including: a lower metal contact including a first metal material, and an upper metal contact disposed on and in contact with the lower metal contact, and including of a second metal material different from the first metal material; a contact spacer

extending from an upper surface of the first dielectric layer to a lower surface of the first dielectric layer, and laterally covering the hybrid metal contact structure; a second dielectric layer disposed on the first dielectric layer; and a via contact penetrating the second dielectric layer and connected to the upper metal contact, the via contact including a metal material which is the same as the second metal material.

16. The semiconductor device according to claim 15, wherein a lower surface of the upper metal contact is in contact with an upper surface of the lower metal contact, and a surface area of the lower surface of the upper metal contact is the same as a surface area of the upper surface of the lower metal contact.

17. The semiconductor device according to claim 15, wherein a lower surface of the upper metal contact is in contact with an upper surface of the lower metal contact, and a surface area of the lower surface of the upper metal contact is greater than a surface area of the upper surface of the lower metal contact.

18. A semiconductor device, comprising: a first dielectric layer; a hybrid metal contact structure disposed in the first dielectric layer, and including: a lower metal contact including a first metal material, and an upper metal contact disposed on and in contact with the lower metal contact, and including of a second metal material different from the first metal material; a contact spacer extending from an upper surface of the first dielectric layer to a lower surface of the first dielectric layer, and laterally covering the hybrid metal contact structure; a gate structure disposed in the first dielectric layer, and separated from the hybrid metal contact structure by the contact spacer; a second dielectric layer disposed on the first dielectric layer; and a via contact penetrating the second dielectric layer and connected to the upper metal contact, the via contact including a metal material which is the same as the second metal material.

19. The semiconductor device according to claim 18, further comprising a protective liner including: a bottom portion disposed below the lower metal contact, and a sidewall portion extending upwardly from a periphery of the bottom portion to laterally cover the lower metal contact.

20. The semiconductor device according to claim 19, wherein a height of the sidewall portion of the protective liner is not greater than a height of the contact spacer.
