

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287778

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

SEO; Satoshi et al.

LIGHT-EMITTING DEVICE AND DISPLAY DEVICE

Abstract

A light-emitting device having favorable characteristics is provided. In a tandem light-emitting device, an electron-transport layer of a light-emitting unit that is the closest to a cathode includes a first organic compound having a triazine skeleton, an intermediate layer includes a second organic compound having a phenanthroline skeleton, light-emitting layers of the light-emitting units include the same emission center substance and the same two kinds of organic compounds that form an exciplex, one or both of the two kinds of organic compounds contain deuterium, the first light-emitting layer is different from a light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device, and the second light-emitting layer is different from a light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

Inventors: SEO; Satoshi (Sagamihara, JP), OHSAWA; Nobuharu (Zama, JP), SEO; Hiromi (Sagamihar, JP), KIDO; Hiromitsu (Atsugi, JP), HAYASHI; Yuki (Atsugi, JP)

Applicant: SEMICONDUCTOR ENERGY LABORATORY CO., LTD. (Atsugi-shi, JP)

Family ID: 1000008521333

Appl. No.: 19/068737

Filed: March 03, 2025

Foreign Application Priority Data

JP	2024-036310	Mar. 08, 2024
----	-------------	---------------

Publication Classification

Int. Cl.: H10K50/19 (20230101); H10K50/125 (20230101); H10K50/16 (20230101);
H10K59/127 (20230101); H10K59/131 (20230101); H10K85/30 (20230101);
H10K85/60 (20230101)

CPC **H10K50/19** (20230201); **H10K50/125** (20230201); **H10K50/16** (20230201);
H10K59/127 (20230201); **H10K59/131** (20230201); **H10K85/342** (20230201);
H10K85/371 (20230201); **H10K85/615** (20230201); **H10K85/633** (20230201);
H10K85/636 (20230201); **H10K85/654** (20230201); **H10K85/656** (20230201);
H10K85/6572 (20230201); **H10K85/6574** (20230201); **H10K85/6576** (20230201);

Background/Summary

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] One embodiment of the present invention relates to an organic compound, an organic semiconductor element, a light-emitting device, a photodiode sensor, a display module, a lighting module, a display device, an electronic appliance, a lighting device, and an electronic device. Note that one embodiment of the present invention is not limited to the above technical field. The technical field of one embodiment of the invention disclosed in this specification and the like relates to an object, a method, or a manufacturing method. One embodiment of the present invention relates to a process, a machine, manufacture, or a composition of matter. Specifically, examples of the technical field of one embodiment of the present invention disclosed in this specification include a semiconductor device, a display device, a liquid crystal display device, a lighting device, a power storage device, a memory device, an image capturing device, a driving method thereof, and a manufacturing method thereof.

2. Description of the Related Art

[0002] A light-emitting device (also referred to as organic EL element) including an organic compound and utilizing electroluminescence (EL) has been put into more practical use. In the basic structure of such a light-emitting device, an organic compound layer including an emission center substance is sandwiched between a pair of electrodes. Carriers are injected by application of a voltage to the device, and recombination energy of the carriers is used, whereby light emission can be obtained from the emission center substance.

[0003] Since such a light-emitting device is of self-luminous type, a display device in which the light-emitting device is used for a pixel has higher visibility than a liquid crystal display device and does not need a backlight. A display device including such a light-emitting device is also highly advantageous in that it can be thin and lightweight. Another feature of such a light-emitting device is that it has an extremely high response speed.

[0004] Since a continuous planar light-emitting layer can be formed for such light-emitting devices, planar light emission can be achieved. This feature is difficult to realize with a point light source typified by an incandescent lamp and an LED or a linear light source typified by a fluorescent lamp; thus, the light-emitting device also has great potential as a planar light source, which can be used for a lighting device and the like.

[0005] Display devices or lighting devices that include light-emitting devices are suitable for a variety of electronic appliances as described above, and research and development of light-emitting devices have progressed for better characteristics.

[0006] Tandem light-emitting devices have attracted particular attention because of their high current efficiency.

[0007] Patent Documents 1 and 2 disclose tandem light-emitting devices fabricated by a side-by-side patterning method.

REFERENCES

SUMMARY OF THE INVENTION

[0010] An object of one embodiment of the present invention is to provide a light-emitting device having favorable characteristics. Another object of one embodiment of the present invention is to provide a light-emitting device having high emission efficiency. Another object of one embodiment of the present invention is to provide a light-emitting device having high reliability. Another object of one embodiment of the present invention is to provide a light-emitting device having a low driving voltage. Another object of one embodiment of the present invention is to provide a light-emitting device having high reliability and a low driving voltage.

[0011] Another object of one embodiment of the present invention is to provide a light-emitting device which enables a display device to have favorable characteristics. Another object of one embodiment of the present invention is to provide a light-emitting device which enables a display device to have high emission efficiency. Another object of one embodiment of the present invention is to provide a light-emitting device which enables a display device to have high reliability. Another object of one embodiment of the present invention is to provide a light-emitting device which enables a display device to have a low driving voltage. Another object of one embodiment of the present invention is to provide a light-emitting device which enables a display device to have high reliability and a low driving voltage.

[0012] Another object of one embodiment of the present invention is to provide any of an organic semiconductor device, a light-emitting device, a light-receiving device, a display device, an electronic appliance, and a lighting device each having low power consumption. Another object of one embodiment of the present invention is to provide an electronic appliance having high reliability or a lighting device having high reliability. Another object of one embodiment of the present invention is to provide any of a novel organic semiconductor device, a novel light-emitting device, a novel light-receiving device, a novel display device, a novel electronic appliance, and a novel lighting device.

[0013] It is only necessary that the present invention achieve at least one of the above-described objects. Note that the description of these objects does not preclude the existence of other objects. One embodiment of the present invention does not need to achieve all these objects. Other objects will be apparent from and can be derived from the description of the specification, the drawings, the claims, and the like.

[0014] One embodiment of the present invention is a light-emitting device including a first electrode, a second electrode, an intermediate layer, a first light-emitting layer, a second light-emitting layer, a first electron-transport layer, and a second electron-transport layer; the intermediate layer is between the first electrode and the second electrode; the first light-emitting layer is between the first electrode and the intermediate layer; the second light-emitting layer is between the intermediate layer and the second electrode; the first electron-transport layer is between the first light-emitting layer and the intermediate layer; the second electron-transport layer is between the second light-emitting layer and the second electrode; the first light-emitting layer includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound or one or both of the fifth organic compound and the sixth organic compound contain deuterium; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; the first light-emitting layer emits light of

a hue different from a hue of light emitted by a light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device; and the second light-emitting layer emits light of a hue different from a hue of light emitted by a light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

[0015] Another embodiment of the present invention is a light-emitting device including a first electrode, a second electrode, an intermediate layer, a first light-emitting layer, a second light-emitting layer, a first electron-transport layer, and a second electron-transport layer; the intermediate layer is between the first electrode and the second electrode; the first light-emitting layer is between the first electrode and the intermediate layer; the second light-emitting layer is between the intermediate layer and the second electrode; the first electron-transport layer is between the first light-emitting layer and the intermediate layer; the second electron-transport layer is between the second light-emitting layer and the second electrode; the first light-emitting layer includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound contain deuterium; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; the first light-emitting layer emits light of a hue different from a hue of light emitted by a light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device; and the second light-emitting layer emits light of a hue different from a hue of light emitted by a light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

[0016] Another embodiment of the present invention is a light-emitting device including a first electrode, a second electrode, an intermediate layer, a first light-emitting layer, a second light-emitting layer, a first electron-transport layer, and a second electron-transport layer; the intermediate layer is between the first electrode and the second electrode; the first light-emitting layer is between the first electrode and the intermediate layer; the second light-emitting layer is between the intermediate layer and the second electrode; the first electron-transport layer is between the first light-emitting layer and the intermediate layer; the second electron-transport layer is between the second light-emitting layer and the second electrode; the second electron-transport layer includes a first organic compound having a triazine skeleton; the intermediate layer includes a mixed layer of a second organic compound having a phenanthroline skeleton and one of lithium and a lithium compound; the first light-emitting layer includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound or one or both of the fifth organic compound and the sixth organic compound contain deuterium; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; the first light-emitting layer includes a light-emitting layer emitting light of a hue different from a hue of light emitted by a light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device; and the second light-emitting layer includes a light-emitting layer emitting light of a hue different from a hue of light emitted by a light-emitting layer of the at least

one of the plurality of light-emitting devices adjacent to the light-emitting device.

[0017] Another embodiment of the present invention is a light-emitting device including a first electrode, a second electrode, an intermediate layer, a first light-emitting layer, a second light-emitting layer, a first electron-transport layer, and a second electron-transport layer; the intermediate layer is between the first electrode and the second electrode; the first light-emitting layer is between the first electrode and the intermediate layer; the second light-emitting layer is between the intermediate layer and the second electrode; the first electron-transport layer is between the first light-emitting layer and the intermediate layer; the second electron-transport layer is between the second light-emitting layer and the second electrode; the second electron-transport layer includes a first organic compound having a triazine skeleton; the intermediate layer includes a mixed layer of a second organic compound having a phenanthroline skeleton and one of lithium and a lithium compound; the first light-emitting layer includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound contain deuterium; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; the first light-emitting layer includes a light-emitting layer emitting light of a hue different from a hue of light emitted by a light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device; and the second light-emitting layer includes a light-emitting layer emitting light of a hue different from a hue of light emitted by a light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

[0018] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes a seventh organic compound having a triazine skeleton.

[0019] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first organic compound and the seventh organic compound are the same organic compound.

[0020] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes an eighth organic compound having no triazine skeleton.

[0021] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes the eighth organic compound having at least one of a pyrimidine skeleton, an imidazole skeleton, and an anthracene skeleton.

[0022] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first organic compound and the seventh organic compound are the same organic compound.

[0023] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the intermediate layer includes lithium or a lithium compound.

[0024] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the intermediate layer includes a mixed layer of the second organic compound and one of the lithium and the lithium compound.

[0025] Another embodiment of the present invention is the light-emitting device having the above structure, in which a difference between a lowest triplet excited level of the third organic compound and a lowest triplet excited level of the fourth organic compound is less than or equal to

0.20 eV.

[0026] Another embodiment of the present invention is the light-emitting device having the above structure, in which a difference between a lowest triplet excited level of the fifth organic compound and a lowest triplet excited level of the sixth organic compound is less than or equal to 0.20 eV.

[0027] Another embodiment of the present invention is the light-emitting device having the above structure, in which the third organic compound and the fourth organic compound form a first exciplex in combination.

[0028] Another embodiment of the present invention is the light-emitting device having the above structure, in which the fifth organic compound and the sixth organic compound form a second exciplex in combination.

[0029] Another embodiment of the present invention is the light-emitting device having the above structure, in which an emission edge on a shorter wavelength side of the first exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of the first emission center substance.

[0030] Another embodiment of the present invention is the light-emitting device having the above structure, in which an emission edge on a shorter wavelength side of the second exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of the second emission center substance.

[0031] Another embodiment of the present invention is the light-emitting device having the above structure, in which the emission edge on a shorter wavelength side of the first exciplex is at a shorter wavelength than the absorption edge on a longer wavelength side of the first emission center substance, and the emission edge on a shorter wavelength side of the second exciplex is at a shorter wavelength than the absorption edge on a longer wavelength side of the second emission center substance.

[0032] Another embodiment of the present invention is the light-emitting device having the above structure, in which a peak wavelength of an emission spectrum of the first exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the first emission center substance, and a difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm.

[0033] Another embodiment of the present invention is the light-emitting device having the above structure, in which a peak wavelength of an emission spectrum of the second exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the second emission center substance, and a difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

[0034] Another embodiment of the present invention is the light-emitting device having the above structure, in which the peak wavelength of the emission spectrum of the first exciplex is on a shorter wavelength side than the peak wavelength of the emission spectrum of the first emission center substance; the difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm; the peak wavelength of the emission spectrum of the second exciplex is on a shorter wavelength side than the peak wavelength of the emission spectrum of the second emission center substance; and the difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

[0035] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first emission center substance and the second emission center substance are the same substance.

[0036] Another embodiment of the present invention is the light-emitting device having the above-

described structure, in which the intermediate layer includes a first layer including the second organic compound.

[0037] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first layer includes lithium or a lithium compound.

[0038] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the intermediate layer further includes a second layer and the second layer is between the first layer and the second light-emitting layer.

[0039] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the second layer includes the fifth organic compound having a hole-transport property.

[0040] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the second layer includes an organic compound having at least one of a halogen group and a cyano group.

[0041] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the second layer includes an organic compound having at least one of fluorine and a cyano group.

[0042] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the second layer includes an organic compound having four or more halogen groups, four or more cyano groups, or a combination of a halogen group(s) and a cyano group(s) the number of which is four or more.

[0043] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the second layer includes an organic compound having four or more fluorines, four or more cyano groups, or a combination of a fluorine(s) and a cyano group(s) the number of which is four or more.

[0044] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes the seventh organic compound having a triazine skeleton.

[0045] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first organic compound and the seventh organic compound are the same organic compound.

[0046] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes the eighth organic compound having no triazine skeleton.

[0047] Another embodiment of the present invention is the light-emitting device having the above-described structure, in which the first electron-transport layer includes the eighth organic compound having at least one of a pyrimidine skeleton, an imidazole skeleton, and an anthracene skeleton.

[0048] Another embodiment of the present invention is a display device including any of the above-described light-emitting devices.

[0049] Another embodiment of the present invention is a display device including a light-emitting device A and a light-emitting device B. In the display device, the light-emitting device A and the light-emitting device B are adjacent to each other; the light-emitting device A includes a first electrode A, a second electrode A, an intermediate layer A, a first light-emitting layer A, a second light-emitting layer A, a first electron-transport layer A, and a second electron-transport layer A; the intermediate layer A is between the first electrode A and the second electrode A; the first light-emitting layer A is between the first electrode A and the intermediate layer A; the second light-emitting layer A is between the intermediate layer A and the second electrode A; the first electron-transport layer A is between the first light-emitting layer A and the intermediate layer A; the second electron-transport layer A is between the second light-emitting layer A and the second electrode A; the light-emitting device B includes a first electrode B, a second electrode B, an intermediate layer

B, a first light-emitting layer B, a second light-emitting layer B, a first electron-transport layer B, and a second electron-transport layer B; the intermediate layer B is between the first electrode B and the second electrode B; the first light-emitting layer B is between the first electrode B and the intermediate layer B; the second light-emitting layer B is between the intermediate layer B and the second electrode B; the first electron-transport layer B is between the first light-emitting layer B and the intermediate layer B; the second electron-transport layer B is between the second light-emitting layer B and the second electrode B; the second electron-transport layer A and the second electron-transport layer B each include a first organic compound having a triazine skeleton; the second electron-transport layer A and the second electron-transport layer B are made of the same material; the intermediate layer A and the intermediate layer B each include a second organic compound having a phenanthroline skeleton and one of lithium and a lithium compound; the first light-emitting layer A includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer A includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound contain deuterium; the first light-emitting layer B includes a third emission center substance; the second light-emitting layer B includes a fourth emission center substance; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; a difference between a maximum peak wavelength of an emission spectrum of the third emission center substance and a maximum peak wavelength of an emission spectrum of the fourth emission center substance is less than or equal to 30 nm; the first light-emitting layer A emits light of a hue different from a hue of light emitted by the first light-emitting layer B; and the second light-emitting layer A emits light of a hue different from a hue of light emitted by the second light-emitting layer B.

[0050] Another embodiment of the present invention is a display device including a light-emitting device A and a light-emitting device B. In the display device, the light-emitting device A and the light-emitting device B are adjacent to each other; the light-emitting device A includes a first electrode A, a second electrode A, an intermediate layer A, a first light-emitting layer A, a second light-emitting layer A, a first electron-transport layer A, and a second electron-transport layer A; the intermediate layer A is between the first electrode A and the second electrode A; the first light-emitting layer A is between the first electrode A and the intermediate layer A; the second light-emitting layer A is between the intermediate layer A and the second electrode A; the first electron-transport layer A is between the first light-emitting layer A and the intermediate layer A; the second electron-transport layer A is between the second light-emitting layer A and the second electrode A; the light-emitting device B includes a first electrode B, a second electrode B, an intermediate layer B, a first light-emitting layer B, a second light-emitting layer B, a first electron-transport layer B, and a second electron-transport layer B; the intermediate layer B is between the first electrode B and the second electrode B; the first light-emitting layer B is between the first electrode B and the intermediate layer B; the second light-emitting layer B is between the intermediate layer B and the second electrode B; the first electron-transport layer B is between the first light-emitting layer B and the intermediate layer B; the second electron-transport layer B is between the second light-emitting layer B and the second electrode B; the second electron-transport layer A and the second electron-transport layer B each include a first organic compound having a triazine skeleton; the second electron-transport layer A and the second electron-transport layer B are one continuous layer; the intermediate layer A and the intermediate layer B each include a second organic compound having a phenanthroline skeleton and one of lithium and a lithium compound; the first

light-emitting layer A includes a first emission center substance, a third organic compound, and a fourth organic compound; the second light-emitting layer A includes a second emission center substance, a fifth organic compound, and a sixth organic compound; the third organic compound and the fifth organic compound each include a π -electron deficient heteroaromatic ring; the fourth organic compound and the sixth organic compound each include a π -electron rich heteroaromatic ring or an aromatic amine skeleton; one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound contain deuterium; the first light-emitting layer B includes a third emission center substance; the second light-emitting layer B includes a fourth emission center substance; a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm; a difference between a maximum peak wavelength of an emission spectrum of the third emission center substance and a maximum peak wavelength of an emission spectrum of the fourth emission center substance is less than or equal to 30 nm; the first light-emitting layer A and the first light-emitting layer B are different from each other; and the second light-emitting layer A and the second light-emitting layer B are different from each other.

[0051] Another embodiment of the present invention is the display device having the above structure, in which a difference between a lowest triplet excited level of the third organic compound and a lowest triplet excited level of the fourth organic compound is less than or equal to 0.20 eV, and a difference between a lowest triplet excited level of the fifth organic compound and a lowest triplet excited level of the sixth organic compound is less than or equal to 0.20 eV.

[0052] Another embodiment of the present invention is the display device having the above structure, in which the third organic compound and the fourth organic compound form the first exciplex in combination, and the fifth organic compound and the sixth organic compound form the second exciplex in combination.

[0053] Another embodiment of the present invention is the display device having the above-described structure, in which the first electron-transport layer includes the seventh organic compound having a triazine skeleton.

[0054] Another embodiment of the present invention is the display device having the above-described structure, in which the first organic compound and the seventh organic compound are the same organic compound.

[0055] Another embodiment of the present invention is the display device having the above-described structure, in which the first electron-transport layer includes the eighth organic compound having no triazine skeleton.

[0056] Another embodiment of the present invention is the display device having the above-described structure, in which the first electron-transport layer includes the eighth organic compound having at least one of a pyrimidine skeleton, an imidazole skeleton, and an anthracene skeleton.

[0057] Another embodiment of the present invention is the display device having the above-described structure, in which the first organic compound and the seventh organic compound are the same organic compound.

[0058] Another embodiment of the present invention is the display device having the above-described structure, in which the intermediate layer includes a mixed layer of the second organic compound and one of the lithium and the lithium compound.

[0059] Another embodiment of the present invention is the display device having the above structure, in which an emission edge on a shorter wavelength side of the first exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of the first emission center substance.

[0060] Another embodiment of the present invention is the display device having the above structure, in which an emission edge on a shorter wavelength side of the second exciplex is at a

shorter wavelength than an absorption edge on a longer wavelength side of the second emission center substance.

[0061] Another embodiment of the present invention is the display device having the above structure, in which the emission edge on a shorter wavelength side of the first exciplex is at a shorter wavelength than the absorption edge on a longer wavelength side of the first emission center substance, and the emission edge on a shorter wavelength side of the second exciplex is at a shorter wavelength than the absorption edge on a longer wavelength side of the second emission center substance.

[0062] Another embodiment of the present invention is the display device having the above structure, in which a peak wavelength of an emission spectrum of the first exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the first emission center substance, and a difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm.

[0063] Another embodiment of the present invention is the display device having the above structure, in which a peak wavelength of an emission spectrum of the second exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the second emission center substance, and a difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

[0064] Another embodiment of the present invention is the display device having the above structure, in which the peak wavelength of the emission spectrum of the first exciplex is on a shorter wavelength side than the peak wavelength of the emission spectrum of the first emission center substance; the difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm; the peak wavelength of the emission spectrum of the second exciplex is on a shorter wavelength side than the peak wavelength of the emission spectrum of the second emission center substance; and the difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

[0065] Another embodiment of the present invention is an electronic appliance including the above-described light-emitting device and a sensor, an operation button, a speaker, or a microphone.

[0066] Another embodiment of the present invention is a lighting device including the above-described light-emitting device and a housing.

[0067] The structures described above are embodiments of the present invention, and the present invention is not limited to the above-described structures.

[0068] One embodiment of the present invention can provide a light-emitting device having favorable characteristics. Another embodiment of the present invention can provide a light-emitting device having high emission efficiency. Another embodiment of the present invention can provide a light-emitting device having high reliability. Another embodiment of the present invention can provide a light-emitting device having a low driving voltage. Another embodiment of the present invention can provide a light-emitting device having high reliability and a low driving voltage.

[0069] Another embodiment of the present invention can provide a light-emitting device which enables a display device to have favorable characteristics. Another embodiment of the present invention can provide a light-emitting device which enables a display device to have high emission efficiency. Another embodiment of the present invention can provide a light-emitting device which enables a display device to have high reliability. Another embodiment of the present invention can provide a light-emitting device which enables a display device to have a low driving voltage.

Another embodiment of the present invention can provide a light-emitting device which enables a

display device to have high reliability and a low driving voltage.

[0070] Another embodiment of the present invention can provide any of an organic semiconductor device, a light-emitting device, a light-receiving device, a display device, an electronic appliance, and a lighting device each having low power consumption. Another embodiment of the present invention can provide an electronic appliance having high reliability or a lighting device having high reliability.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0071] In the accompanying drawings:

[0072] FIGS. 1A to 1C are schematic views of light-emitting devices of embodiments of the present invention;

[0073] FIGS. 2A and 2B are schematic views of light-emitting devices of embodiments of the present invention;

[0074] FIGS. 3A and 3B illustrate a display device of one embodiment of the present invention;

[0075] FIGS. 4A and 4B illustrate a display device of one embodiment of the present invention;

[0076] FIGS. 5A to 5E are cross-sectional views illustrating an example of a method for manufacturing a display device;

[0077] FIGS. 6A and 6B are cross-sectional views illustrating the example of the method for manufacturing the display device;

[0078] FIGS. 7A to 7D are cross-sectional views illustrating the example of the method for manufacturing the display device;

[0079] FIGS. 8A to 8C are cross-sectional views illustrating the example of the method for manufacturing the display device;

[0080] FIGS. 9A to 9C are cross-sectional views illustrating the example of the method for manufacturing the display device;

[0081] FIGS. 10A to 10C are cross-sectional views illustrating the example of the method for manufacturing the display device;

[0082] FIGS. 11A and 11B are perspective views illustrating a structure example of a display module;

[0083] FIGS. 12A and 12B are cross-sectional views illustrating structure examples of a display device;

[0084] FIG. 13 is a perspective view illustrating a structure example of a display device;

[0085] FIG. 14 is a cross-sectional view illustrating a structure example of a display device;

[0086] FIG. 15 is a cross-sectional view illustrating a structure example of a display device;

[0087] FIGS. 16A to 16C illustrate a structure example of a display device;

[0088] FIG. 17 is a cross-sectional view illustrating a structure example of a display device;

[0089] FIGS. 18A to 18C illustrate a structure example of a display device;

[0090] FIGS. 19A to 19D illustrate examples of wearable devices;

[0091] FIGS. 20A to 20F illustrate examples of electronic appliances;

[0092] FIGS. 21A to 21G illustrate examples of electronic appliances;

[0093] FIG. 22 shows a method for calculating emission lifetime;

[0094] FIG. 23 shows the luminance-current density characteristics of a light-emitting device R1 and a comparative light-emitting device R1;

[0095] FIG. 24 shows the current efficiency-luminance characteristics of the light-emitting device R1 and the comparative light-emitting device R1;

[0096] FIG. 25 shows the current density-voltage characteristics of the light-emitting device R1 and the comparative light-emitting device R1;

[0097] FIG. **26** shows the power efficiency-luminance characteristics of the light-emitting device **R1** and the comparative light-emitting device **R1**;

[0098] FIG. **27** shows electroluminescence spectra of the light-emitting device **R1** and the comparative light-emitting device **R1**;

[0099] FIG. **28** shows the luminance-current density characteristics of light-emitting devices **G1** to **G3** and a comparative light-emitting device **G1**;

[0100] FIG. **29** shows the current efficiency-luminance characteristics of the light-emitting devices **G1** to **G3** and the comparative light-emitting device **G1**;

[0101] FIG. **30** shows current density-voltage characteristics of the light-emitting devices **G1** to **G3** and the comparative light-emitting device **G1**;

[0102] FIG. **31** shows the power efficiency-luminance characteristics of the light-emitting devices **G1** to **G3** and the comparative light-emitting device **G1**;

[0103] FIG. **32** shows electroluminescence spectra of the light-emitting devices **G1** to **G3** and the comparative light-emitting device **G1**;

[0104] FIG. **33** shows the luminance-current density characteristics of a light-emitting device **B1** and a comparative light-emitting device **B1**;

[0105] FIG. **34** shows the current efficiency-luminance characteristics of the light-emitting device **B1** and the comparative light-emitting device **B1**;

[0106] FIG. **35** shows the current density-voltage characteristics of the light-emitting device **B1** and the comparative light-emitting device **B1**;

[0107] FIG. **36** shows the power efficiency-luminance characteristics of the light-emitting device **B1** and the comparative light-emitting device **B1**;

[0108] FIG. **37** shows the blue index-luminance characteristics of the light-emitting device **B1** and the comparative light-emitting device **B1**;

[0109] FIG. **38** shows electroluminescence spectra of the light-emitting device **B1** and the comparative light-emitting device **B1**;

[0110] FIG. **39** shows PL spectra of 8mpTP-4mDBtPBfpm-d.sub.13, β NCCP-d.sub.26, and an exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26;

[0111] FIG. **40** shows a PL spectrum of an exciplex of 8mpTP-4mDBtPBfpm and β NCCP and an absorption spectrum and a PL spectrum of Ir(5mpppy-d.sub.3).sub.2(mbfppy-d.sub.3);

[0112] FIG. **41** shows an example of determining an emission edge and an absorption edge;

[0113] FIG. **42** shows the time dependence of normalized luminance of the light-emitting devices **G1** to **G3** and the comparative light-emitting device **G1**;

[0114] FIG. **43** shows a method for measuring a T.sub.1 level of 8mpTP-4mDBtPBfpm-d.sub.13;

[0115] FIG. **44** shows a method for measuring a T.sub.1 level of 8mpTP-4mDBtPBfpm;

[0116] FIG. **45** shows a method for measuring a T.sub.1 level of β NCCP-d.sub.26;

[0117] FIG. **46** shows a method for measuring a T.sub.1 level of β NCCP;

[0118] FIG. **47** shows the luminance-current density characteristics of a light-emitting device **R4**, a light-emitting device **G4**, and a light-emitting device **B4**;

[0119] FIG. **48** shows the current efficiency-luminance characteristics of the light-emitting device **R4**, the light-emitting device **G4**, and the light-emitting device **B4**;

[0120] FIG. **49** shows current density-voltage characteristics of the light-emitting device **R4**, the light-emitting device **G4**, and the light-emitting device **B4**;

[0121] FIG. **50** shows the power efficiency-luminance characteristics of the light-emitting device **R4**, the light-emitting device **G4**, and the light-emitting device **B4**;

[0122] FIG. **51** shows the blue index-current density characteristics of the light-emitting device **B4**;

[0123] FIG. **52** shows electroluminescence spectra of the light-emitting device **R4**, the light-emitting device **G4**, and the light-emitting device **B4**;

[0124] FIG. **53** shows a PL spectrum of an exciplex of 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 and an absorption spectrum and a PL spectrum of Pt(tBudppymmtBubiz-tBubp);

[0125] FIG. 54 shows an example of determining an absorption edge of Pt(tBudppymmtBubiz-tBubp);

[0126] FIG. 55 shows PL spectra of 11mDBtBPPnfpr, β NCCP-d.sub.26, and an exciplex of 11mDBtBPPnfpr and β NCCP-d.sub.26;

[0127] FIG. 56 shows a PL spectrum of the exciplex of 11mDBtBPPnfpr and β NCCP-d.sub.26 and an absorption spectrum and a PL spectrum of OCPG-006; and

[0128] FIG. 57 shows an example of determining an absorption edge of OCPG-006.

DETAILED DESCRIPTION OF THE INVENTION

[0129] Embodiments of the present invention will be described in detail below with reference to the drawings. Note that the present invention is not limited to the following description, and it will be readily appreciated by those skilled in the art that modes and details of the present invention can be modified in various ways without departing from the spirit and scope of the present invention. Thus, the present invention should not be construed as being limited to the description in the following embodiments.

[0130] In this specification and the like, a device formed using a metal mask or a fine metal mask (FMM, a high-resolution metal mask) is sometimes referred to as a device having a metal mask (MM) structure. In this specification and the like, a device formed without using a metal mask or an FMM is sometimes referred to as a device having a metal maskless (MML) structure.

[0131] In this specification and the like, “containing deuterium” means that the proportion of deuterium in an organic compound containing hydrogen and deuterium is much higher than, specifically, 500 times or more the natural abundance of deuterium, and a “deuterated organic compound” refers to an organic compound where the proportion of deuterium in an organic compound containing hydrogen and deuterium is much higher than, specifically, 500 times or more the natural abundance of deuterium. Note that this proportion is not a proportion in one molecule, but is an average proportion in a plurality of target organic compounds in a certain area.

Embodiment 1

[0132] A tandem light-emitting device has a structure in which a plurality of light-emitting units are stacked between a pair of electrodes with an intermediate layer (a charge-generation layer) between the plurality of light-emitting units. The plurality of light-emitting units include their respective light-emitting layers, and each of the light-emitting layers can emit light with a flow of current therethrough. The tandem light-emitting device having such a structure has much higher current efficiency than a non-tandem light-emitting device, and can thus be suitably used for a display device that is required to perform high-luminance display or that needs to have high reliability.

[0133] Since the tandem light-emitting device includes a plurality of light-emitting layers and can thus easily provide white light emission, many full-color display devices including the tandem light-emitting device employ a “white+color filter” method. A color conversion method is also in practical use in which light-emitting layers that emit blue light are stacked and a color conversion layer typified by quantum dots is used.

[0134] Meanwhile, some full-color display devices employing a side-by-side patterning method and the tandem light-emitting device have also been put into practical use. A light-emitting device fabricated by the side-by-side patterning method has little or no energy loss due to a color filter or a color conversion layer and can thus have a higher emission efficiency than light-emitting devices fabricated by the above-described two methods.

[0135] At least one of light-emitting layers included in a tandem light-emitting device of one embodiment of the present invention includes an emission center substance, a first host material, and a second host material. The emission center substance is preferably a phosphorescent substance. In the case of a light-emitting device in which excitation is caused by current, the light-emitting device can have high emission efficiency when using a substance that can convert triplet energy into light emission (a phosphorescent substance or a substance exhibiting thermally activated delayed fluorescence) as a light-emitting substance (guest material).

[0136] In another known structure, two kinds of organic compounds (specifically, an organic compound with an electron-transport property and an organic compound with a hole-transport property) are used as host materials in combination with a light-emitting substance (guest material) in a light-emitting layer.

[0137] In particular, a technology using a structure where an exciplex formed by two kinds of organic compounds is used as an energy donor and a substance that can convert triplet energy into light emission (a phosphorescent substance or a substance exhibiting thermally activated delayed fluorescence) is used as an energy acceptor in a light-emitting layer, which is called exciplex-triplet energy transfer (ExTET), is a capable technology that can achieve high efficiency, a low driving voltage, and a long lifetime.

[0138] That is, a light-emitting device whose light-emitting layer contains an exciplex as an energy donor and a substance that can convert triplet energy into light emission as an energy acceptor, i.e., a light-emitting substance, can have excellent characteristics.

[0139] When one or both of the two kinds of substances (the first host material and the second host material) functioning as the host materials contain deuterium, the light-emitting device can have higher reliability.

[0140] In particular, as described later, in the case where the difference in the lowest triplet excited level (T.sub.1 level) between the first and second host materials is small, that is, in the case where the T.sub.1 levels of the first and second host materials are close to each other, the triplet excitation energy is less likely to be localized in one of the organic compounds, and energy transfer from the organic compounds in triplet excited states to the substance that can convert triplet energy into light emission might occur. The efficiency of the energy transfer from the organic compounds is improved by the influence of deuterium, whereby deterioration of the first host material and the second host material one or both of which contain deuterium can be inhibited.

[0141] This effect is significant particularly when the two kinds of substances form an exciplex. The singlet excitation energy of the exciplex is transferred from the exciplex to the light-emitting substance. Meanwhile, the triplet excitation energy can be transferred not only directly to the light-emitting substance but also indirectly to the light-emitting substance through the first or second host material in the triplet excited state. In particular, as described later, in the case where the difference in the lowest triplet excited level (T.sub.1 level) between the first and second host materials is small, that is, in the case where the T.sub.1 levels of the first and second host materials are close to each other, energy transfer through the organic compounds in the triplet excited states to the substance that can convert triplet energy into light emission might occur. This is because the excitation energy is less likely to be localized in one of the organic compounds. The efficiency of the energy transfer from the organic compounds in the triplet excited states is improved by the influence of deuterium, whereby deterioration of the first and second host materials can be inhibited. Specifically, the difference in the T.sub.1 level between the first and second host materials is preferably less than or equal to 0.20 eV.

[0142] Accordingly, a light-emitting device in which an exciplex formed partly by a deuterated organic compound is used as an energy donor can have less deterioration than a light-emitting device in which an exciplex formed only by non-deuterated organic compounds is used as an energy donor, and thus can have high reliability.

[0143] Although all the hydrogens in the molecule may be replaced with deuterium in one or both of the first host material and the second host material, at least a group or a skeleton where the lowest triplet excited level is localized is deuterated, and hydrogen contained in any of the other groups or skeletons is preferably protium. This enables the first or second host material to be obtained at low cost as compared with the case where all the hydrogens in the molecule is replaced with deuterium.

[0144] Note that the first host material has an electron-transport property, and preferably includes a π -electron deficient heteroaromatic ring. The second host material has a hole-transport property,

and preferably includes a π -electron rich heteroaromatic ring or an aromatic amine skeleton.

[0145] In the light-emitting device of one embodiment of the present invention, an improvement in energy transfer efficiency due to one or both of the first and second host materials containing deuterium is derived from the phosphorescence lifetime or delayed fluorescence lifetime of a deuterated organic compound which is longer than that of a non-deuterated organic compound. This is because a deuterated organic compound in the lowest triplet excited state (T.sub.1 state) has less intramolecular vibration than a non-deuterated organic compound in the T.sub.1 state and accordingly has less non-radiative transition from the T.sub.1 state to a more stable state.

[0146] The energy transfer efficiency ϕ_{ET} from an energy donor (an exciplex in one embodiment of the present invention) to an energy acceptor (a substance that can convert triplet excitation energy into light emission in one embodiment of the present invention) is expressed by Formula (1) below. According to this formula, it is found that the energy transfer efficiency ϕ_{ET} can be increased by increasing the rate constant $k_{\text{h}^* \rightarrow \text{g}}$ of energy transfer so that another competing rate constant $k_{\text{r}} + k_{\text{nr}} (=1/\tau)$ becomes relatively small.

[0147] In Formula (1), k_{r} represents the rate constant of a light emission process (fluorescence in the case where energy transfer from a singlet excited state is discussed, and phosphorescence or delayed fluorescence in the case where energy transfer from a triplet excited state is discussed) of the energy donor, k_{nr} represents the rate constant of a non-light-emission process (thermal deactivation and intersystem crossing) of the energy donor, and τ represents a measured lifetime of an excited state of the energy donor. In addition, $k_{\text{h}^* \rightarrow \text{g}}$ represents the rate constant of energy transfer (Forster mechanism or Dexter mechanism).

[Formula1]

$$[00001] \quad \phi_{\text{ET}} = \frac{k_{\text{h}^* \rightarrow \text{g}}}{k_{\text{r}} + k_{\text{nr}} + k_{\text{h}^* \rightarrow \text{g}}} = \frac{k_{\text{h}^* \rightarrow \text{g}}}{(1/\tau) + k_{\text{h}^* \rightarrow \text{g}}} \quad (1)$$

[0148] A deuterated organic compound and a non-deuterated organic compound have substantially the same atomic arrangement in a molecule and substantially the same spectrum shape, for example, and thus have substantially the same rate constant $k_{\text{h}^* \rightarrow \text{g}}$ of energy transfer (see Formula (2) or (3) below). Thus, in comparison between the deuterated organic compound and the non-deuterated organic compound, the rate constant $k_{\text{h}^* \rightarrow \text{g}}$ of energy transfer is found to be greatly affected by the emission lifetime (phosphorescence lifetime or delayed fluorescence lifetime) τ . That is, the energy transfer efficiency is improved as the emission lifetime (phosphorescence lifetime or delayed fluorescence lifetime) is longer.

[Formula2]

$$[00002] \quad k_{\text{h}^* \rightarrow \text{g}} = \frac{9000 K^2 \phi_{\text{h}} \ln 10}{128 \pi^4 N^2 R^6} \int \frac{f_{\text{h}}(\nu) g(\nu)}{\nu^4} d\nu \quad (2)$$

[Formula3]

$$k_{\text{h}^* \rightarrow \text{g}} = \left(\frac{2}{h}\right) K^2 \exp\left(-\frac{2R}{L}\right) \int f_{\text{h}}(\nu) g(\nu) d\nu \quad (3)$$

[0149] Formula (2) is a formula of the rate constant $k_{\text{h}^* \rightarrow \text{g}}$ of the Forster mechanism and Formula (3) is a formula of the rate constant $k_{\text{h}^* \rightarrow \text{g}}$ of the Dexter mechanism.

[0150] In Formula (2), ν represents a frequency, $f_{\text{h}}(\nu)$ represents a normalized emission spectrum of the host material (a fluorescent spectrum in the case where energy transfer from a singlet excited state is discussed, and a phosphorescent spectrum in the case where energy transfer from a triplet excited state is discussed), $\epsilon_{\text{g}}(\nu)$ represents a molar absorption coefficient of the guest material, N represents Avogadro's number, n represents a refractive index of a medium, R represents an intermolecular distance between the host material and the guest material, τ represents a measured lifetime of an excited state (fluorescence lifetime or phosphorescence lifetime), ϕ represents an emission quantum yield (a fluorescence quantum yield in the case where energy transfer from a singlet excited state is discussed, and a phosphorescence quantum yield in the case where energy transfer from a triplet excited state is discussed), and K_{D} represents a coefficient

(0 to 4) of orientation of a transition dipole moment between the host material and the guest material. Note that $K_{\text{sup.2}}$ is $\frac{2}{3}$ in random orientation.

[0151] In Formula (3), h represents a Planck constant, K represents a constant having an energy dimension, ν represents a frequency, $f'_{\text{sub.h}}(\nu)$ represents a normalized emission spectrum of the host material (a fluorescent spectrum in the case where energy transfer from a singlet excited state is discussed, and a phosphorescent spectrum in the case where energy transfer from a triplet excited state is discussed), $\epsilon'_{\text{sub.g}}(\nu)$ represents a normalized absorption spectrum of the guest material, L represents an effective molecular radius, and R represents an intermolecular distance between the host material and the guest material.

[0152] As described above, in energy transfer from the first and second host materials, the efficiency of energy transfer from the triplet excited state is important and thus the lifetime of the triplet excited state is important. In other words, when one or both of the first host material and the second host material are deuterated, the phosphorescence lifetime or delayed fluorescence lifetime is extended to improve the energy transfer efficiency, whereby deterioration of the deuterated organic compound(s) can be inhibited. Accordingly, a light-emitting device including an energy donor formed by deuterated organic compounds has less deterioration of the organic compounds than a light-emitting device including an energy donor formed by non-deuterated organic compounds, and thus can have high reliability.

[0153] The phosphorescence lifetime and the delayed fluorescence lifetime are calculated by measuring the transient PL by time-resolved measurement, in which the emission intensity attenuating after the excitation light is blocked by a shutter is measured at certain intervals. In this measurement, a graph is sometimes not linear because fluorescence components are mixed at the initial stage of attenuation. In such a case, a starting point is set in a portion where the graph is straight, and the time taken for the intensity at the starting point to attenuate to $1/e$ is regarded as the phosphorescence lifetime or the delayed fluorescence lifetime.

[0154] Note that an exciplex formed by the first and second host materials preferably serves as an energy donor in the light-emitting device of one embodiment of the present invention, and as described above, the triplet excitation energy can be transferred from the exciplex in the triplet excited state to the light-emitting substance through the first and second host materials in the triplet excited states; thus, the phosphorescence lifetimes or delayed fluorescence lifetimes of the first and second host materials forming the exciplex are important. It was found that in the light-emitting device of one embodiment of the present invention utilizing the exciplex as the energy donor, one of the first and second host materials, preferably both of them, contain deuterium to have the phosphorescence lifetimes or the delayed fluorescence lifetimes longer than a certain length, and thus the reliability of the light-emitting device improves significantly.

[0155] That is, the phosphorescence lifetime or delayed fluorescence lifetime of the organic compound as the first host material is preferably 1.50 times or more that of the first host material that is not deuterated. The phosphorescence lifetime or delayed fluorescence lifetime of the organic compound as the second host material is preferably 3.00 times or more that of the second host material that is not deuterated. In this case, it is preferable that light emitted from the substance that can convert triplet excitation energy into light emission (the light-emitting substance contained in the light-emitting layer) be in the green region, that is, the peak wavelength be typically greater than or equal to 500 nm and less than or equal to 600 nm.

[0156] From the measurement data shown in the left graph in FIG. 22, the starting point is set as $t=0$ within the range where the graph is straight (here, the time at which the light amount becomes 50% of that at the start of the measurement is set as $t=0$) (the right graph in FIG. 22). The time taken for the light amount to attenuate to $1/e$ of that at $t=0$ is regarded as the phosphorescence lifetime or the delayed fluorescence lifetime. In the right graph of FIG. 22, the time at which the intensity reaches 50% of that at the start of the measurement is set as time 0 s, the light amount at 0 s is regarded as 1, and the time taken for the light amount to become $1/e$ is the phosphorescence

lifetime or the delayed fluorescence lifetime. Although the point where the intensity becomes 50% of that at the start of the measurement is easily used as the starting point, a point with another intensity may be used as the starting point.

[0157] The phosphorescence lifetime can be measured at liquid nitrogen temperature (77 K) with a fluorescence spectrophotometer such as FP-8600 produced by JASCO Corporation, in which a liquid nitrogen cooling unit is set. A solution of a material is prepared in a glove box in the following manner: a sample is dissolved in 2-MeTHF that has been deoxidized, and then stirring is performed with a stirrer at room temperature for approximately 30 minutes (heating is also performed in the case where the material has low solubility) so that the concentration of the solution is adjusted to approximately 1.2 E.sup.-4 M.

[0158] The time-resolved measurement can be performed in the following manner: a sample cell is irradiated with excitation light for approximately 30 seconds and the emission intensity attenuating after the excitation light is blocked by a shutter is measured at 10 ms intervals. The peak wavelength of the phosphorescent spectrum is preferably used for measuring the phosphorescence lifetime. In the case where the phosphorescent spectrum has a plurality of peaks, a wavelength with the highest peak intensity is preferably selected. Depending on the wavelength, the measurement cannot be performed accurately because of a mixed fluorescence spectrum in some cases. In such a case, an emission spectrum (including phosphorescence components) measured at low temperature (e.g., 77 K) and an emission spectrum (including only fluorescence components and not including phosphorescence components) measured at normal temperature are compared, and a phosphorescence wavelength of the emission spectrum not overlapping with the fluorescence spectrum as much as possible is preferably selected. Alternatively, a wavelength of a peak on the longest wavelength side in the phosphorescent spectrum can be selected. In the case of a frozen solution, light emission from a state other than the lowest triplet excited state is also observed in some cases. In this case, a wavelength of a peak on the longest wavelength side is selected.

[0159] Note that the excitation wavelength is appropriately selected within a wavelength range where a solvent has no influence. As long as the material can be excited sufficiently, measurement is preferably performed at a wavelength of 330 nm because there is no influence by a solvent. The band widths of excitation light and measured light are each approximately 10 nm. Ideally, light emission attenuates single-exponentially; thus, a starting point is set in a portion where a graph is straight, and the time taken for the intensity at the starting point to attenuate to 1/e can be defined as the phosphorescence lifetime or the delayed fluorescence lifetime.

[0160] Note that the fluorescence lifetime can be distinguished from the phosphorescence lifetime and the delayed fluorescence lifetime by the length of the lifetime in time-resolved measurement. An emission lifetime on the order of nanoseconds is the fluorescence lifetime, and an emission lifetime on the order of microseconds to milliseconds or more is the phosphorescence lifetime or the delayed fluorescence lifetime.

[0161] The reliability of the light-emitting device of one embodiment of the present invention is improved in accordance with an increase in the phosphorescence lifetime, i.e., the lifetime of triplet excitons, of the first and second host materials. The increase in the lifetime of triplet excitons is caused by inhibited non-radiative deactivation of the triplet excitation energy, which is due to inhibited vibration owing to deuteration. At this time, the difference in the T.sub.1 level between the first and second host materials is preferably small, in which case the excitation energy is less likely to be localized in one of the organic compounds and thus significant deterioration of one of the organic compounds can be prevented, leading to high reliability of the light-emitting device. Specifically, the difference in the T.sub.1 level between the first and second host materials is preferably less than or equal to 0.20 eV, further preferably less than or equal to 0.15 eV, still further preferably less than or equal to 0.10 eV.

[0162] Note that for calculation of the lowest triplet excited level (T.sub.1 level), an emission spectrum (a phosphorescent spectrum) is measured at a measurement temperature of 10 K using a

50-nm-thick thin film of a sample formed over a quartz substrate. The measurement is preferably performed with a PL microscope (LabRAM HR-PL, produced by HORIBA, Ltd.) and a He—Cd laser (325 nm) as excitation light. Note that the emission edge can be determined as the intersection between a tangent and the horizontal axis (representing wavelength) or the baseline. The tangent is drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the emission spectrum (phosphorescent spectrum) has the maximum absolute value.

[0163] In one embodiment of the present invention, the sublimation temperature of the first host material is preferably close to that of the second host material. For example, the difference between the 5% weight loss temperature of the first host material measured by thermogravimetry and the 5% weight loss temperature of the second host material measured by thermogravimetry is preferably less than or equal to 60° C., further preferably less than or equal to 45° C., still further preferably less than or equal to 20° C., yet still further preferably less than or equal to 10° C. This enables evaporation using a mixed material of the first and second host materials, thereby reducing the number of evaporation sources and providing a light-emitting device with favorable characteristics at low cost.

[0164] The 5% weight loss temperature can be obtained from the relation between weight and temperature (thermogravimetric measurement) by performing thermogravimetry-differential thermal analysis (TG-DTA). In the case where the pressure for the evaporation is determined in advance, it is preferable to use a value measured under the pressure.

[0165] By combining a preferable increasing rate of a phosphorescence lifetime or a delayed fluorescence lifetime owing to deuteration, a preferable product of the increasing rates of the first and second host materials, a preferable difference in T.sub.1 level, and a preferable difference in sublimation temperature, a light-emitting device with better characteristics can be obtained.

[0166] In addition, the photoluminescence (PL) spectrum of the exciplex formed by the first and second host materials and that of the light-emitting substance (the substance that can convert triplet energy into light emission) preferably include an overlap. This is because the driving voltage of the light-emitting device can be reduced when the excitation energy of the energy donor is close to the excitation energy of the light-emitting substance. Thus, the difference between the maximum peak wavelengths is preferably less than or equal to 30 nm. Alternatively, the difference in the wavelength of the emission edge on a shorter wavelength side of the PL spectrum between the exciplex and the light-emitting substance is preferably less than or equal to 30 nm, in which case the driving voltage of the light-emitting device can be decreased.

[0167] The PL spectrum of the exciplex is preferably measured using a film formed by co-evaporation of the first and second host materials. A sample used for measuring the PL spectrum of the light-emitting substance (the substance that can convert triplet energy into light emission) may be in the form of a thin film or a solution, but is preferably in the form of a solution for examination of the state of an isolated molecule. There is no particular limitation on a solvent of the solution as long as the same solvent is used for a comparison between the PL spectra. A solvent with relatively low polarity, such as toluene or chloroform, is preferable.

[0168] In the case where the substance that can convert triplet excitation energy into light emission (the light-emitting substance contained in the light-emitting layer) emits light in the blue region, that is, in the case where the peak wavelength is typically greater than or equal to 450 nm and less than 500 nm, the first host material is preferably an organic compound that includes at least one of a triazine skeleton and a diazine skeleton, and the second host material is preferably an organic compound that includes a carbazole skeleton. A specific example of the first host material is 9,9'-{6-[3-(triphenylsilyl)phenyl]-1,3,5-triazine-2,4-diyl}bis(9H-carbazole-1,2,3,4,5,6,7,8,1',2',3',4',5',6',7',8'-d.sub.16) (abbreviation: SiTrzCz2-d.sub.16). Specific examples of the second host material include 9-[3-(triphenylsilyl)phenyl]-3,9'-(bi-9H-carbazole-d.sub.15) (abbreviation: PSiCzCz-dis), 9'-(phenyl-d.sub.15)-9'H-9,3':6',9''-tercarbazole-

1,1',1'',2,2',2'',3,3'',4,4',4'',5,5',5'',6,6'',7,7',7'',8,8',8''-d.sub.22 (abbreviation: PhCzGI-d.sub.27), and 9'-[3-(triphenylsilyl)phenyl]-9'H-9,3':6',9''-tercarbazole-1,1',1'',2,2',2'',3,3'',4,4',4'',5,5',5'',6,6'',7,7',7'',8,8',8''-d.sub.22 (abbreviation: PSiCzGI-d.sub.22). [0169] In the case where the substance that can convert triplet excitation energy into light emission (the light-emitting substance contained in the light-emitting layer) emits light in the green region, that is, in the case where the peak wavelength is typically greater than or equal to 500 nm and less than or equal to 600 nm, the first host material is preferably an organic compound that includes at least one of a diazine skeleton and a triazine skeleton, and the second host material is preferably an organic compound that includes a carbazole skeleton. Specific examples of the first host material include 8-(1,1':4,1''-terphenyl-3-yl-2,4,5,6,2',3',5',6',2'',3'',4'',5'',6''-d.sub.13)-4-[3-(dibenzothiophen-4-yl-1,2,3,6,7,8,9-d.sub.7)phenyl-2,4,6-d.sub.3]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm-d.sub.23), 8-(1,1':4,1''-terphenyl-3-yl-2,4,5,6,2',3',5',6',2'',3'',4'',5'',6''-d.sub.13)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm-d.sub.13), and 11-[4-(biphenyl-4-yl-2,2',3,3',4',5,5',6,6'-d.sub.9)-6-(phenyl-2,3,4,5,6-d.sub.5)-1,3,5-triazin-2-yl]-11,12-dihydro-12-(biphenyl-3-yl)indolo[2,3-a]carbazole-1,2,3,4,5,6,7,8,9,10-d.sub.10. Specific examples of the second host material include 9-(2-naphthyl-1,3,4,5,6,7,8-d.sub.7)-9'-(phenyl-2,3,4,5,6-d.sub.5)-3,3'-bi-9H-carbazole-1,1',2,2',4,4',5,5',6,6',7,7',8,8'-d.sub.4 (abbreviation: β NCCP-d.sub.26) and 9-phenyl-9'-(phenyl-2,3,4,5,6-d.sub.5)-3,3'-bis(9H-carbazole) (abbreviation: PCCP-d.sub.5).

[0170] Since the light-emitting device of one embodiment of the present invention is a tandem light-emitting device, a plurality of light-emitting layers are included. Although the structure of the light-emitting layer described above may be applied to only some of the light-emitting layers, it is preferable that all the light-emitting layers have this structure.

[0171] For example, in the case of a tandem light-emitting device including a first light-emitting layer and a second light-emitting layer, it is preferable that the first light-emitting layer include a first emission center substance, a third organic compound, and a fourth organic compound, the second light-emitting layer include a fifth organic compound and a sixth organic compound, one or both of the third organic compound and the fourth organic compound be deuterated, and one or both of the fifth organic compound and the sixth organic compound be deuterated. It is preferable that the third organic compound and the fifth organic compound each correspond to the first host material, the fourth organic compound and the sixth organic compound each correspond to the second host material, and the first light-emitting layer and the second light-emitting layer each have the above structure of the light-emitting layer.

[0172] Specifically, it is preferable that each of the third organic compound and the fifth organic compound have an electron-transport property and include a π -electron deficient heteroaromatic ring. It is preferable that each of the fourth organic compound and the sixth organic compound have a hole-transport property and include a π -electron rich heteroaromatic ring or an aromatic amine skeleton. The third organic compound and the fourth organic compound preferably form an exciplex in combination, and the fifth organic compound and the sixth organic compound preferably form an exciplex in combination. The difference in the T.sub.1 level between the third organic compound and the fourth organic compound and the difference in the T.sub.1 level between the fifth organic compound and the sixth organic compound are each preferably less than or equal to 0.20 eV, further preferably less than or equal to 0.15 eV, still further preferably less than or equal to 0.10 eV. The other structures described above can be employed for the light-emitting layers by replacing the first host material with the third organic compound or the fifth organic compound and replacing the second host material with the fourth organic compound or the sixth organic compound.

[0173] The formation of an exciplex can be confirmed by a phenomenon in which the emission spectrum of the mixed film in which the organic compound having a hole-transport property and

the organic compound having an electron-transport property are mixed is on a longer wavelength side than the emission spectrum of each of the organic compounds (or has another peak on a longer wavelength side) observed by comparison of the emission spectra of the organic compound having a hole-transport property, the organic compound having an electron-transport property, and the mixed film of these organic compounds, for example. Alternatively, the formation of an exciplex can be confirmed by a difference in transient response, such as a phenomenon in which the transient photoluminescence (PL) lifetime of the mixed film has longer lifetime components or has a larger proportion of delayed components than that of each of the organic compounds, observed by comparison of transient PL of the organic compound having a hole-transport property, the organic compound having an electron-transport property, and the mixed film of these organic compounds. The transient PL can be rephrased as transient electroluminescence (EL). That is, the formation of an exciplex can also be confirmed by a difference in transient response observed by comparison of the transient EL of the organic compound having a hole-transport property, the organic compound having an electron-transport property, and the mixed film of these organic compounds.

[0174] In that case, the emission edge on a shorter wavelength side of a PL spectrum of the exciplex formed by the first host material and the second host material is preferably positioned at a shorter wavelength than the absorption edge on a longer wavelength side of the absorption spectrum of the emission center substance. When the PL spectrum of the exciplex and the absorption edge of the emission center substance have such a positional relation, energy can be efficiently transferred.

[0175] Alternatively, the peak wavelength of the PL spectrum of the exciplex formed by the first host material and the second host material is preferably shorter than the peak wavelength of the PL spectrum of the emission center substance. The difference between the peak wavelength of the PL spectrum of the exciplex and the peak wavelength of the PL spectrum of the emission center substance is further preferably less than or equal to 30 nm. When the peak wavelengths of the PL spectra of the exciplex and the emission center substance have such a relation, energy can be efficiently transferred.

[0176] Alternatively, the difference between the peak wavelength of the PL spectrum of the exciplex formed by the first host material and the second host material and the wavelength of the absorption edge on a longer wavelength side of the absorption spectrum of the emission center substance is preferably less than or equal to 30 nm. When the peak wavelength of the PL spectrum of the exciplex and the wavelength of the absorption edge on a longer wavelength side of the absorption spectrum of the emission center substance have such a relation, energy can be efficiently transferred.

[0177] The PL spectrum of the exciplex is preferably measured using a film formed by co-evaporation of the first and second host materials. Meanwhile, the PL spectrum or the absorption spectrum of the emission center substance may be measured using a sample in the form of a thin film or a solution; however, the sample is preferably in the form of a solution for examination of the state of an isolated molecule. As a solvent of the solution, a solvent with relatively low polarity, such as toluene or chloroform, is preferable.

[0178] The absorption edge of the absorption spectrum can be determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent is drawn at a point at which the slope on a longer wavelength side of the longest-wavelength peak (or the longest-wavelength shoulder peak) of the absorption spectrum has the maximum absolute value. The emission edge on a shorter wavelength side of the PL spectrum can be determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent is drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the PL spectrum has the maximum absolute value.

[0179] In one embodiment of the present invention, it is preferable that the first host material be an organic compound having an electron-transport property and the second host material be an organic

compound having a hole-transport property as described above.

[0180] The organic compound having an electron-transport property, which is the first host material, preferably has an electron mobility higher than or equal to 1×10^{-7} cm²/Vs, further preferably higher than or equal to 1×10^{-6} cm²/Vs when the square root of the electric field strength [V/cm] is 600.

[0181] The organic compound having an electron-transport property is preferably an organic compound having a π -electron deficient heteroaromatic ring. Examples of the organic compound having a π -electron deficient heteroaromatic ring include an organic compound that has a heteroaromatic ring having an azole skeleton, an organic compound that has a heteroaromatic ring having a pyridine skeleton, an organic compound that has a heteroaromatic ring having a diazine skeleton, and an organic compound that has a heteroaromatic ring having a triazine skeleton.

[0182] Among the above organic compounds, the organic compound that has a heteroaromatic ring having a diazine skeleton (a pyrimidine skeleton, a pyrazine skeleton, or a pyridazine skeleton), the organic compound that has a heteroaromatic ring having a pyridine skeleton, and the organic compound that has a heteroaromatic ring having a triazine skeleton are preferable because of their high reliability. In particular, the organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton and the organic compound that has a heteroaromatic ring having a triazine skeleton have a high electron-transport property to contribute to a reduction in driving voltage. A benzofuropyrimidine skeleton, a benzothenopyrimidine skeleton, a benzofuopyrazine skeleton, and a benzothenopyrazine skeleton are preferable because of their high acceptor properties and high reliability.

[0183] Preferable examples of the organic compound with a π -electron deficient heteroaromatic ring that can be used as the organic compound having an electron-transport property include the following organic compounds: organic compounds having an azole skeleton, such as 2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole (abbreviation: PBD), 3-(4-biphenyl)-4-phenyl-5-(4-tert-butylphenyl)-1,2,4-triazole (abbreviation: TAZ), 1,3-bis[5-(p-tert-butylphenyl)-1,3,4-oxadiazol-2-yl]benzene (abbreviation: OXD-7), 9-[4-(5-phenyl-1,3,4-oxadiazol-2-yl)phenyl]-9H-carbazole (abbreviation: CO11), 2,2',2''-(1,3,5-benzenetriyl)tris(1-phenyl-1H-benzimidazole) (abbreviation: TPBI), 2-[3-(dibenzothiophen-4-yl)phenyl]-1-phenyl-1H-benzimidazole (abbreviation: mDBTBI-II), and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene (abbreviation: BzOS); organic compounds that have a heteroaromatic ring having a pyridine skeleton, such as 3,5-bis[3-(9H-carbazol-9-yl)phenyl]pyridine (abbreviation: 35DCzPPy), 1,3,5-tri[3-(3-pyridyl)phenyl]benzene (abbreviation: TmPyPB), bathophenanthroline (abbreviation: BPhen), bathocuproine (abbreviation: BCP), 2,9-di(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline (abbreviation: NBPhen), 2,2'-(1,3-phenylene)bis(9-phenyl-1,10-phenanthroline) (abbreviation: mPPhen2P), 2-[3-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: mTpPPhen), 2-phenyl-9-(2-triphenylenyl)-1,10-phenanthroline (abbreviation: Ph-TpPhen), 2-[4-(9-phenanthrenyl)-1-naphthalenyl]-1,10-phenanthroline (abbreviation: PnNPhen), and 2-[4-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: pTpPPhen); organic compounds having a diazine skeleton, such as 2-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 2mDBTPDBq-II), 2-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mDBTBPDq-II), 2-[3'-(9H-carbazol-9-yl)biphenyl-3-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mCzBPDBq), 2-[4'-(9-phenyl-9H-carbazol-3-yl)-3,1'-biphenyl-1-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mpPCBPDBq), 2-[4-(3,6-diphenyl-9H-carbazol-9-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 2CzPDBq-III), 7-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 7mDBTPDBq-II), 6-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 6mDBTPDBq-II), 9-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]naphtho[1',2':4,5]furo[2,3-b]pyrazine (abbreviation: 9mDBtBPNfpr), 9-[3'-(dibenzothiophen-4-yl)biphenyl-4-yl]naphtho[1',2':4,5]furo[2,3-b]pyrazine (abbreviation: 9pmDBtBPNfpr), 4,6-bis[3-(phenanthren-9-yl)phenyl]pyrimidine (abbreviation:

4,6mPnP2Pm), 4,6-bis[3-(dibenzothiophen-4-yl)phenyl]pyrimidine (abbreviation: 4,6mDBTP2Pm-II), 4,6-bis[3-(9H-carbazol-9-yl)phenyl]pyrimidine (abbreviation: 4,6mCzP2Pm), 9,9'-[pyrimidine-4,6-diylbis(biphenyl-3,3'-diyl)]bis(9H-carbazole) (abbreviation: 4,6mCzBP2Pm), 8-(biphenyl-4-yl)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8BP-4mDBtPBfpm), 3,8-bis[3-(dibenzothiophen-4-yl)phenyl]benzofuro[2,3-b]pyrazine (abbreviation: 3,8mDBtP2Bfpr), 4,8-bis[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 4,8mDBtP2Bfpm), 8-[3'-(dibenzothiophen-4-yl)(biphenyl-3-yl)]naphtho[1',2':4,5]furo[3,2-d]pyrimidine (abbreviation: 8mDBtBPNfpm), 8-[(2,2'-binaphthalen)-6-yl]-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8(PN2)-4mDBtPBfpm), 2,2'-(pyridine-2,6-diyl)bis(4-phenylbenzo[h]quinazoline) (abbreviation: 2,6(P-Bqn)2Py), 2,2'-(pyridine-2,6-diyl)bis{4-[4-(2-naphthyl)phenyl]-6-phenylpyrimidine} (abbreviation: 2,6(NP-PPm)2Py), 6-(biphenyl-3-yl)-4-[3,5-bis(9H-carbazol-9-yl)phenyl]-2-phenylpyrimidine (abbreviation: 6mBP-4Cz2PPm), 2,6-bis(4-naphthalen-1-ylphenyl)-4-[4-(3-pyridyl)phenyl]pyrimidine (abbreviation: 2,4NP-6PyPPm), 4-[3,5-bis(9H-carbazol-9-yl)phenyl]-2-phenyl-6-(biphenyl-4-yl)pyrimidine (abbreviation: 6BP-4Cz2PPm), 7-[4-(9-phenyl-9H-carbazol-2-yl)quinazolin-2-yl]-7H-dibenzo[c,g]carbazole (abbreviation: PC-cgDBCzQz), 8-(p-terphenyl-3-yl)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm), and 2,2'-(2,2'-bipyridine-6,6'-diyl)bis(4-phenylbenzo[h]quinazoline) (abbreviation: 6,6'(P-Bqn)2BPY); organic compounds that have a heteroaromatic ring having a triazine skeleton, such as 2-(biphenyl-4-yl)-4-phenyl-6-(9,9'-spirobi[9H-fluoren]-2-yl)-1,3,5-triazine (abbreviation: BP-SFTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-8-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-6-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn-02), 2-{4-[3-(N-phenyl-9H-carbazol-3-yl)-9H-carbazol-9-yl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: PCCzPTzn), 9-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-9'-phenyl-2,3'-bi-9H-carbazole (abbreviation: mPCCzPTzn-02), 2-[3'-(9,9-dimethyl-9H-fluoren-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mFBPTzn), 5-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-7,7-dimethyl-5H,7H-indeno[2,1-b]carbazole (abbreviation: mINc(II)PTzn), 2-{3-[3-(dibenzothiophen-4-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mDBtBPTzn), 2,4,6-tris[3'-(pyridin-3-yl)biphenyl-3-yl]-1,3,5-triazine (abbreviation: TmPPPyTz), 2-[3-(2,6-dimethyl-3-pyridinyl)-5-(9-phenanthrenyl)phenyl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mPn-mDMePyPTzn), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-phenylindolo[2,3-a]carbazole (abbreviation: BP-Icz(II)Tzn), 2-[3'-(triphenylen-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mTpBPTzn), 3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]-9-phenyl-9H-carbazole (abbreviation: PCDBfTzn), 2-[4-(2-naphthalenyl)phenyl]-4-phenyl-6-spiro[9H-fluorene-9,9'-[9H]xanthen]-4-yl-1,3,5-triazine (abbreviation: PNP-SFx(4)Tzn), 9,9'-{6-[3-(triphenylsilyl)phenyl]-1,3,5-triazine-2,4-diyl}bis(9H-carbazole) (abbreviation: SiTrzCz2), 2-phenyl-4,6-bis[3-(triphenylsilyl)phenyl]-1,3,5-triazine (abbreviation: mSiTrz), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-(biphenyl-3-yl)indolo[2,3-a]carbazole (abbreviation: BP-mBPIcz(II)Tzn), 3-{3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]phenyl}-9-phenyl-9H-carbazole (abbreviation: mPCPDBfTzn), 9,9'-[6-(biphenyl-4-yl)-2-phenyl-1,3,5-triazine-4,3''-diyl]bis(9H-carbazole) (abbreviation: Cz-pmCzBPTzn), 2-(biphenyl-3-yl)-4-phenyl-6-{8-[(1,1':4',1''-terphenyl)-4-yl]-1-dibenzofuranyl}-1,3,5-triazine (abbreviation: mBP-TPDBfTzn), 3-phenyl-9-[4-phenyl-6-(9-phenyl-3-dibenzofuranyl)-1,3,5-triazin-2-yl]-9H-carbazole (abbreviation: PDBf-PCzTzn), 9-[4-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzothienyl]-2-phenyl-9H-carbazole (abbreviation: PCzDBtTzn), and 2,4,6-tris(2-pyridyl)-1,3,5-triazine (abbreviation: 2Py3Tzn). Note that in the case where the first host material is an organic compound containing deuterium, any of the above organic compounds in which some or all of hydrogens are replaced with deuterium can be used. It is particularly preferable to use an organic compound in which a group or a skeleton where a triplet

excited level is localized is deuterated.

[0184] The organic compound having a hole-transport property, which is the second host material, is preferably an organic compound having an amine skeleton or a π -electron rich heteroaromatic ring, for example. As the π -electron rich heteroaromatic ring, a condensed aromatic ring having at least one of an acridine skeleton, a phenoxazine skeleton, a phenothiazine skeleton, a furan skeleton, a thiophene skeleton, and a pyrrole skeleton in the ring is preferable; specifically, a carbazole ring, a dibenzothiophene ring, or a ring in which an aromatic ring or a heteroaromatic ring is further condensed to a carbazole ring or a dibenzothiophene ring is preferable.

[0185] Such an organic compound having a hole-transport property further preferably has any of a carbazole skeleton, a dibenzofuran skeleton, a dibenzothiophene skeleton, and an anthracene skeleton. In particular, an aromatic amine having a substituent that has a dibenzofuran ring or a dibenzothiophene ring, an aromatic monoamine that has a naphthalene ring, or an aromatic monoamine in which a 9-fluorenyl group is bonded to nitrogen of an amine through an arylene group may be used. Note that the substance having a hole-transport property is preferably an organic compound having an N,N-bis(4-biphenyl)amino group to enable fabricating a light-emitting device having a long lifetime.

[0186] Preferable examples of such organic compounds include the following organic compounds: compounds having an aromatic amine skeleton, such as 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (abbreviation: NPB), N,N-diphenyl-N,N-bis(3-methylphenyl)-4,4'-diaminobiphenyl (abbreviation: TPD), N,N'-bis(9,9'-spirobi[9H-fluoren]-2-yl)-N,N-diphenyl-4,4'-diaminobiphenyl (abbreviation: BSPB), 4-phenyl-4'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: BPAFLP), 4-phenyl-3'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: mBPAFLP), 4-phenyl-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBA1BP), 4,4'-diphenyl-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBBi1BP), 4-(1-naphthyl)-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBANB), 4,4'-di(1-naphthyl)-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBNBB), 9,9-dimethyl-N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]fluoren-2-amine (abbreviation: PCBAF), and N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: PCBASF); compounds having a carbazole skeleton, such as 1,3-bis(N-carbazolyl)benzene (abbreviation: mCP), 4,4'-di(N-carbazolyl)biphenyl (abbreviation: CBP), 3,6-bis(3,5-diphenylphenyl)-9-phenylcarbazole (abbreviation: CzTP), 3,3'-bis(9-phenyl-9H-carbazole) (abbreviation: PCCP), 3,9-bis(9-phenyl-9H-carbazol-3-yl)-9H-carbazole (abbreviation: PCCzPC), 9-(biphenyl-4-yl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: PCCzBP), 9,9'-bis(biphenyl-4-yl)-3,3'-bi-9H-carbazole (abbreviation: BisBPCz), 9,9'-bis(biphenyl-3-yl)-3,3'-bi-9H-carbazole (abbreviation: BismBPCz), 9-(biphenyl-3-yl)-9'-(biphenyl-4-yl)-9H,9'H-3,3'-bicarbazole (abbreviation: mBPCCBP), 9-(2-naphthyl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: β NCCP), 9-(3-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCmBP), 9-(4-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCBP), 9,9'-di-2-naphthyl-3,3'-9H,9'H-bicarbazole (abbreviation: BisPNCz), 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-5-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-phenyl-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole (abbreviation: PCCzTp), 9,9'-bis(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(4-biphenyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(triphenylen-2-yl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-1-amine, 9-[3-(triphenylsilyl)phenyl]-3,9'-bi-9H-carbazole (abbreviation: PSiCzCz), and 9'-[3-(triphenylsilyl)phenyl]-9'H-9,3':6',9''-tercarbazole (abbreviation: PSiCzGI); compounds having a thiophene skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzothiophene) (abbreviation: DBT3P-II), 2,8-diphenyl-4-[4(9-phenyl-9H-fluoren-9-

yl)phenyl]dibenzothiophene (abbreviation: DBTFLP-III), and 4-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]-6-phenyldibenzothiophene (abbreviation: DBTFLP-IV); and compounds having a furan skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzofuran) (abbreviation: DBF3P-II) and 4-{3-[3-(9-phenyl-9H-fluoren-9-yl)phenyl]phenyl}dibenzofuran (abbreviation: mmDBFFLBI-II). Among the above compounds, the compound having an aromatic amine skeleton and the compound having a carbazole skeleton are preferable because these compounds are highly reliable and have a high hole-transport property to contribute to a reduction in driving voltage. Note that in the case where the second host material is an organic compound containing deuterium, any of the above organic compounds in which some or all of hydrogens are replaced with deuterium can be used. It is particularly preferable to use an organic compound in which a group or a skeleton where a triplet excited level is localized is deuterated.

[0187] As described above, it is preferable that the first host material be an organic compound having an electron-transport property and the second host material be an organic compound having a hole-transport property. For a higher carrier-transport property and more efficient exciplex formation, it is preferable that the first host material be an organic compound having a π -electron deficient heteroaromatic ring and the second host material be an organic compound having an amine skeleton or a π -electron rich heteroaromatic ring. Alternatively, for higher triplet excitation energy, it is preferable that the first host material be an organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton or an organic compound that has a heteroaromatic ring having a triazine skeleton and the second host material be an organic compound that has any of a carbazole skeleton, a dibenzofuran skeleton, a dibenzothiophene skeleton, and an anthracene skeleton. For higher stability and reliability, it is preferable that the first host material be an organic compound having a triazine skeleton or a pyrimidine skeleton and the second host material be an organic compound having a carbazole skeleton. As the organic compound having a carbazole skeleton, it is particularly preferable to use an organic compound having a 3,3'-bicarbazole skeleton because the organic compound has a high donor property and high heat resistance. It is extremely preferable that the second host material be the organic compound having a 3,3'-bicarbazole skeleton and the first host material be the organic compound having a triazine skeleton, in which case high triplet excitation energy, stability, and reliability are achieved.

[0188] Note that by mixing the organic compound having an electron-transport property with the organic compound having a hole-transport property, the transport property of the light-emitting layer can be easily adjusted and a recombination region can be easily controlled. The weight ratio of the content of the organic compound having a hole-transport property to the content of the organic compound having an electron-transport property is 1:19 to 19:1, preferably 3:7 to 7:3.

[0189] The light-emitting layer included in the tandem light-emitting device is preferably separated from a light-emitting layer included in at least one adjacent light-emitting device. Alternatively, the light-emitting layer included in the tandem light-emitting device is preferably different from a light-emitting layer included in at least one adjacent light-emitting device. Alternatively, the emission color of the tandem light-emitting device or a pixel including the tandem light-emitting device is preferably different from the emission color of at least one adjacent light-emitting device or pixel. Alternatively, the emission center substance included in the light-emitting layer of the tandem light-emitting device preferably has a structure different from that of an emission center substance included in a light-emitting layer of at least one adjacent light-emitting device.

[0190] Note that in the tandem light-emitting device of one embodiment of the present invention, it is preferable that the electron-transport layer included in the light-emitting unit on the cathode side include a first organic compound having a triazine skeleton and the intermediate layer include a second organic compound having a phenanthroline skeleton. When the electron-transport layer of the light-emitting unit on the cathode side includes the first organic compound and the intermediate layer includes the second organic compound, the tandem light-emitting device can achieve low

driving voltage. When the electron-transport layer of the light-emitting unit on the cathode side includes the first organic compound, the intermediate layer includes the second organic compound, and any one of the light-emitting layers includes the emission center substance as well as the first host material and the second host material one or both of which are deuterated, the tandem light-emitting device can achieve lower driving voltage. In addition, the emission efficiency is further improved, whereby the light-emitting device can have high power efficiency and high energy efficiency.

[0191] Moreover, when the light-emitting layer included in the tandem light-emitting device is separated from a light-emitting layer included in at least one adjacent light-emitting device or is different from a light-emitting layer included in at least one adjacent light-emitting device, the emission color of the tandem light-emitting device is different from the emission color of at least one adjacent light-emitting device, or the emission center substance included in the light-emitting layer of the tandem light-emitting device has a structure different from that of an emission center substance included in a light-emitting layer of at least one adjacent light-emitting device as described above, the tandem light-emitting device can have extremely high current efficiency and can thus have higher power efficiency and higher energy efficiency.

[0192] As a result, a display device of one embodiment of the present invention that includes such a light-emitting device can achieve low power consumption, high reliability, high-luminance display, and high visibility. In addition, the display device can have high display quality.

[0193] The above-described first organic compound having a triazine skeleton preferably has an electron mobility higher than or equal to 1×10^{-7} cm²/Vs, further preferably higher than or equal to 1×10^{-6} cm²/Vs when the square root of the electric field strength [V/cm] is 600. Note that any other substance can also be used as long as the substance has a property of transporting more electrons than holes.

[0194] The first organic compound having a triazine skeleton preferably has the triazine skeleton and an aromatic ring. The aromatic ring is preferably a monocyclic aromatic ring, a polycyclic aromatic ring, an aromatic ring having an alkyl group as a substituent, an aromatic ring having a fluoro group as a substituent, an aromatic ring having a cyano group as a substituent, or the like. The triazine skeleton may have a substituent other than the above-described aromatic ring, and the aromatic ring may have a substituent other than the above-described fluoro group, cyano group, or alkyl group. Note that the triazine skeleton is also referred to as a triazine ring, and other skeletons can also be rephrased as rings.

[0195] Examples of the monocyclic aromatic ring include aromatic hydrocarbon rings such as a benzene ring and heteroaromatic rings such as a pyrrole ring, a pyridine ring, a pyrimidine ring, and a triazine ring. Having the aromatic ring as a substituent has the effect of improving heat resistance, specifically, a glass transition temperature (T_{sub.g}), and the effect of improving an electron-transport property, for example.

[0196] Examples of the polycyclic aromatic ring include aromatic hydrocarbon rings such as a naphthalene ring, a phenanthrene ring, a chrysene ring, a triphenylene ring, a fluorene ring, and a spirobifluorene ring and heteroaromatic rings such as a carbazole ring, a dibenzofuran ring, a dibenzothiophene ring, a xanthene ring, an indolocarbazole ring, and an indenocarbazole ring. A compound having the polycyclic aromatic ring as a substituent can improve heat resistance more than a compound having the monocyclic aromatic ring such as a benzene ring and is thus preferable. A compound having as a substituent a ring in which an aromatic ring (e.g., a benzene ring, a naphthalene ring, or a pyridine ring) is further condensed to any of the above polycyclic aromatic rings can further improve heat resistance. Examples of the ring in which an aromatic ring is further condensed to the polycyclic aromatic ring include a benzofluorene ring, a benzonaphthofuran ring, a benzoxanthene ring, and a benzonaphthothiophene ring. Providing a layer including a compound having high heat resistance in the vicinity of the cathode can inhibit heat damage to the device when high-temperature treatment in a patterning step or the like is

performed after the layer or the cathode is formed.

[0197] Examples of the alkyl group include a methyl group, an ethyl group, a propyl group, a tertiary butyl group, a cyclohexyl group, and an adamantyl group. The first organic compound having the alkyl group as a substituent can have a low refractive index, and a layer including the first organic compound can have a low refractive index. This can inhibit total reflection at the interface between the layer and another layer and improve the light extraction efficiency of the light-emitting device including the layer. When such a compound having an alkyl group is used also for the hole-transport layer, the refractive index of the hole-transport layer can be lowered. In particular, when a compound having a triazine skeleton and an alkyl group is used for the electron-transport layer and a compound having an aromatic amine skeleton and an alkyl group is used for the hole-transport layer, the effect of improving the light extraction efficiency can be synergistically enhanced. An organic compound having an alkyl group having a plurality of carbon atoms, preferably three or more carbon atoms, further preferably four or more carbon atoms, still further preferably five or more carbon atoms, can enhance the effect of lowering the refractive index. A layer including a compound having a fluoro group as a substituent is also preferable because it can lower the refractive index. In particular, an organic compound having a plurality of fluoro groups can enhance the effect of lowering the refractive index. It is also effective to use a compound having a fluoro group for both the electron-transport layer and the hole-transport layer. A compound having a structure in which a plurality of alkyl groups or fluoro groups are bonded to one aromatic ring can further lower the refractive index of the layer. In one example, two or three or more tertiary butyl groups are bonded as substituents to one benzene ring. Without limitation to the benzene ring, the plurality of alkyl groups or fluoro groups may be bonded to another monocyclic aromatic ring such as a pyridine ring or a polycyclic aromatic ring such as a fluorene ring. In addition, the plurality of alkyl groups or fluoro groups are suitably bonded to one or more rings included in a polycyclic aromatic ring (e.g., a naphthalene ring, a fluorene ring, a carbazole ring, a quinoline ring, or a xanthene ring). In one example, a plurality of tertiary butyl groups are bonded to one benzene ring included in a fluorene ring.

[0198] The first organic compound having a cyano group as a substituent is preferable because it can improve the electron-transport property.

[0199] A combination of some of polycyclic aromatic rings, alkyl groups, fluoro groups, and cyano groups is also suitable for substituents of the first organic compound. Having a polycyclic aromatic ring and a cyano group as substituents, for example, can improve both the heat resistance and the electron-transport property. In addition, having a polycyclic aromatic ring and an alkyl group can improve both the heat resistance and the light extraction efficiency. In this manner, substituents can be combined in accordance with the required function.

[0200] The first organic compound having a plurality of polycyclic aromatic rings as substituents can further improve the heat resistance. In that case, the first organic compound preferably has the aromatic hydrocarbon ring and the heteroaromatic ring.

[0201] The first organic compound having a triazine skeleton can be specifically, for example, an organic compound that has a heteroaromatic ring having a triazine skeleton, such as 2-(biphenyl-4-yl)-4-phenyl-6-(9,9'-spirobi[9H-fluoren]-2-yl)-1,3,5-triazine (abbreviation: BP-SFTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-8-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-6-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn-02), 2-{4-[3-(N-phenyl-9H-carbazol-3-yl)-9H-carbazol-9-yl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: PCCzPTzn), 9-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-9'-phenyl-2,3'-bi-9H-carbazole (abbreviation: mPCCzPTzn-02), 2-[3'-(9,9-dimethyl-9H-fluoren-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mFBPTzn), 5-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-7,7-dimethyl-5H,7H-indeno[2,1-b]carbazole (abbreviation: mINc(II)PTzn), 2-{3-[3-(dibenzothiophen-4-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mDBtBPTzn), 2,4,6-tris[3'-(pyridin-3-yl)biphenyl-3-yl]-1,3,5-triazine (abbreviation:

TmPPyTz), 2-[3-(2,6-dimethyl-3-pyridinyl)-5-(9-phenanthrenyl)phenyl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mPn-mDMePyPTzn), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-phenylindolo[2,3-a]carbazole (abbreviation: BP-Icz(II)Tzn), 2-[3'-(triphenyl-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mTpBPTzn), 3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]-9-phenyl-9H-carbazole (abbreviation: PCDBfTzn), 2-(biphenyl-3-yl)-4-phenyl-6-{8-[(1,1':4',1''-terphenyl)-4-yl]-1-dibenzofuranyl}-1,3,5-triazine (abbreviation: mBP-TPDBfTzn), 2-[4-(2-naphthalenyl)phenyl]-4-phenyl-6-spiro[9H-fluoren-9,9'-[9H]xanthen]-4-yl-1,3,5-triazine (abbreviation: PNP-SFx(4)Tzn), 9,9'-{6-[3-(triphenylsilyl)phenyl]-1,3,5-triazine-2,4-diyl}bis(9H-carbazole) (abbreviation: SiTrzCz2), 2-phenyl-4,6-bis[3-(triphenylsilyl)phenyl]-1,3,5-triazine (abbreviation: mSiTrz), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-(biphenyl-3-yl)indolo[2,3-a]carbazole (abbreviation: BP-mBPIcz(II)Tzn), 3-{3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]phenyl}-9-phenyl-9H-carbazole (abbreviation: mPCPDBfTzn), 9,9'-[6-(biphenyl-4-yl)-2-phenyl-1,3,5-triazine-4,3''-diyl]bis(9H-carbazole) (abbreviation: Cz-pmCzBPTzn), 3-phenyl-9-[4-phenyl-6-(9-phenyl-3-dibenzofuranyl-1,3,5-triazin-2-yl)-9H-carbazole (abbreviation: PDBf-PCzTzn), 9-[4-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzothienyl]-2-phenyl-9H-carbazole (abbreviation: PCzDBtTzn), 2,4-diphenyl-6-[3'-(spiro[7H-benzo[c]fluorene-7,9'-[9H]xanthen]-2'-yl)biphenyl-3-yl]-1,3,5-triazine (abbreviation: mSbfxBPTzn), 3'-[4-phenyl-6-(spiro[9H-fluorene-9,9'-[9H]xanthen]-2'-yl)-1,3,5-triazin-2-yl]biphenyl-4-carbonitrile (abbreviation: mpCNBP-SFxTzn), or 2,2'-[1,2-naphthalenediyl]di(4,1-phenylene)]bis(4,6-diphenyl-1,3,5-triazine) (abbreviation: TznP2N), and is particularly preferably TznP2N represented by Structural Formula (100) below, mSbfxBPTzn represented by Structural Formula (101) below, mpCNBP-SFxTzn represented by Structural Formula (102) below, CNBPNTzn represented by Structural Formula (103) below, PNP-SFx(4)Tzn represented by Structural Formula (104) below, mmtBuBP-mDMePyPTzn represented by Structural Formula (105) below, mBnfBPTzn represented by Structural Formula (106) below, or the like.

##STR00001## ##STR00002##

[0202] Note that an electron-transport layer included in a light-emitting unit on the anode side may include a seventh organic compound having a triazine skeleton, like the electron-transport layer included in the light-emitting unit on the cathode side, or may include an eighth organic compound having no triazine skeleton.

[0203] The electron-transport layer included in the light-emitting unit on the anode side preferably includes the seventh organic compound having a triazine skeleton in order to reduce power consumption. It is particularly preferable that the seventh organic compound included in the electron-transport layer be the same as the first organic compound in order to inhibit a manufacturing apparatus from becoming complex and offer a cost advantage in raw material procurement.

[0204] When the electron-transport layer included in the light-emitting unit on the anode side includes the eighth organic compound having no triazine skeleton, the carrier-transport property can be easily controlled to provide a light-emitting device with better characteristics. The organic compound not having a triazine skeleton is preferably an organic compound that has a heteroaromatic ring having a pyridine skeleton or an organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton. Note that any of the above organic compounds deuterated as appropriate can also be used.

[0205] The above-described second organic compound having a phenanthroline skeleton and included in the intermediate layer preferably has an electron mobility higher than or equal to 1×10^{-7} cm²/Vs, further preferably higher than or equal to 1×10^{-6} cm²/Vs when the square root of the electric field strength [V/cm] is 600. Note that any other substance can also be used as long as the substance has a property of transporting more electrons than holes.

[0206] The second organic compound having a phenanthroline skeleton preferably has the

phenanthroline skeleton and an aromatic ring. The aromatic ring is preferably a monocyclic aromatic ring, a polycyclic aromatic ring, or the like.

[0207] Examples of the monocyclic aromatic ring include a benzene ring, a pyrrole ring, a pyridine ring, and a pyrimidine ring. Preferable examples of the polycyclic aromatic ring include heteroaromatic rings such as a phenanthroline ring and a pyrrole ring, as well as aromatic hydrocarbon rings such as a naphthalene ring, a phenanthrene ring, a chrysene ring, a triphenylene ring, and a fluorene ring. It is particularly preferable that the second organic compound have a plurality of such polycyclic aromatic rings to improve its heat resistance or electron-transport property.

[0208] The second organic compound having a phenanthroline skeleton can be, for example, an organic compound that has a heteroaromatic ring having a phenanthroline skeleton, such as bathophenanthroline (abbreviation: BPhen), bathocuproine (abbreviation: BCP), 2,9-di(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline (abbreviation: NBPhen), 2,2'-(1,3-phenylene)bis(9-phenyl-1,10-phenanthroline) (abbreviation: mPPhen2P), 2-[3-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: mTpPPhen), 2-phenyl-9-(2-triphenylenyl)-1,10-phenanthroline (abbreviation: Ph-TpPPhen), 2-[4-(9-phenanthrenyl)-1-naphthalenyl]-1,10-phenanthroline (abbreviation: PnNPhen), or 2-[4-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: pTpPPhen), and is preferably PnNPhen represented by Structural Formula (200) below, mPPhen2P represented by (201) below, or the like.

##STR00003##

[0209] In the light-emitting device of one embodiment of the present invention, the intermediate layer can have any structure as long as it includes the second organic compound having a phenanthroline skeleton and can inject electrons and holes respectively into the light-emitting unit on the anode side and the light-emitting unit on the cathode side, which are in contact with the intermediate layer, by voltage application between the anode and the cathode. Note that the intermediate layer preferably has a stacked-layer structure of a first layer including the second organic compound and a second layer positioned closer to the cathode than the first layer is.

[0210] The first layer preferably includes a metal or a metal compound in addition to the second organic compound. The metal or a metal of the metal compound is preferably an alkali metal (Group 1 element) such as Li, an alkaline earth metal (Group 2 element) such as Mg or Ca, a Group 3 element including Y and lanthanoids such as Eu and Yb, a Group 11 element such as Cu, Ag, or Au, a Group 12 element such as Zn, an earth metal (Group 13 element) such as Al or In.

[0211] Note that the first layer may have a stacked-layer structure of a layer including an organic compound and a layer including a metal or a metal compound and positioned closer to the cathode than the layer including an organic compound is, or may be a mixed layer of an organic compound and a metal or a metal compound. The first layer is preferably the mixed layer, in which case it requires a smaller number of film formation chambers and a lower manufacturing cost and contributes to an improvement in the stability of the light-emitting device.

[0212] In the case where the organic compound and the metal or the metal compound are mixed, the organic compound and the metal or the metal compound tend to show substantially the same distribution when the first layer is analyzed in the thickness direction. That is, when the organic compound is uniformly distributed, the metal or the metal compound is also substantially uniformly distributed. In the case of the stacked-layer structure of the layer including the organic compound and the layer including the metal or the metal compound, the metal or the metal compound is sometimes diffused from the layer including the metal or the metal compound and detected also in a region other than the layer but shows a distribution different from that of the organic compound; thus, the analysis results of diffusion and mixing can be distinguished from each other.

[0213] In the case where the metal or the metal compound is detected over a region having a thickness greater than or equal to 10 nm, preferably greater than or equal to 15 nm, further

preferably greater than or equal to 20 nm when the first layer is analyzed in the thickness direction, the first layer can be regarded as including a mixed layer in which the organic compound and the metal or the metal compound are mixed.

[0214] The metal or a metal of the metal compound is preferably, among others, a substance exhibiting a donor property with respect to the second organic compound. Examples of the substance exhibiting a donor property with respect to the second organic compound include metals belonging to Groups 1 and 2; lithium or a lithium compound is particularly preferable. Specifically, Li, lithium fluoride (LiF), lithium oxide (Li.sub.2O), 8-hydroxyquinolino-lithium (abbreviation: Liq), or the like is preferable. In the case where the first layer includes the second organic compound and the substance exhibiting a donor property with respect to the second organic compound, electrons are generated by charge separation, and the electrons are injected into the light-emitting unit on the anode side through the second organic compound when voltage is applied between the anode and the cathode. Thus, the light-emitting device of one embodiment of the present invention can have a low driving voltage.

[0215] The second organic compound is preferably an organic compound having a phenanthroline skeleton having an electron-donating substituent, as well as the above-described organic compound. The phenanthroline skeleton is likely to interact with the metal or the like, and when the second organic compound having such a phenanthroline skeleton further has an electron-donating group, the phenanthroline skeleton can have a higher electron density and become more likely to interact with the metal or the metal compound. In particular, the use of a metal belonging to Group 3, 11, 12, or 13 as the metal or a metal of the metal compound makes it possible to provide a tandem light-emitting device which is inhibited from having an increase in driving voltage and which has favorable characteristics.

[0216] Specific examples of the electron-donating group include an alkyl group, an alkoxy group, an aryloxy group, an alkylamino group, an arylamino group, and a heterocyclic amino group. Note that examples of the electron-donating group that is preferably introduced to the phenanthroline ring are not limited to the above examples. The electron-donating group may be any group that can increase the electron density of the phenanthroline ring by being introduced to the phenanthroline ring. The electron-donating group may be introduced to the phenanthroline ring via an arylene group such as a phenylene group, and the arylene group is preferably a p-phenylene group.

[0217] Specific examples of the organic compound that can be used as the second organic compound are shown in Structural Formulae (300) to (311).

##STR00004## ##STR00005##

[0218] Note that the first layer preferably includes a Group 1 or Group 2 element, especially lithium or a lithium compound, and the second organic compound having a phenanthroline skeleton having an electron-donating substituent, in which case the tandem light-emitting device can have a lower driving voltage and higher reliability. Moreover, the first layer preferably includes a Group 1 or Group 2 element, especially lithium or a lithium compound, and the second organic compound having a phenanthroline skeleton having an electron-donating substituent, in which case it is possible to inhibit an increase in driving voltage due to processing of an organic compound layer of the light-emitting device by a photolithography method.

[0219] Among organic compounds having a phenanthroline ring, an organic compound having a 1,10-phenanthroline ring, the two nitrogen atoms of which can be coordinated to a metal, is particularly preferably used as the second organic compound in the intermediate layer having the above-described structure to facilitate interaction with the metal or the metal compound.

[0220] In the case where an electron-donating group is introduced to a 1,10-phenanthroline skeleton, the electron-donating group is preferably substituted at the 4- and 7-positions of the 1,10-phenanthroline skeleton. Introducing electron-donating groups to the 4- and 7-positions of the 1,10-phenanthroline skeleton can increase the electron density of the nitrogen atoms at the 1- and 10-positions, thereby facilitating the interaction with the metal or the metal compound.

[0221] The first layer may further include an organic compound different from the second organic compound. Note that the different organic compound preferably has an electron-transport property. It is particularly preferable that the organic compound have two or more heteroaromatic rings bonded or condensed to each other and the two or more heteroaromatic rings have three or more heteroatoms in total. The first layer including such an organic compound can improve the heat resistance, the electron-transport property, and the like.

[0222] The second layer preferably includes a ninth organic compound having a hole-transport property. The second layer preferably further includes a substance exhibiting an acceptor property, and the substance exhibiting an acceptor property is preferably an organic compound exhibiting an acceptor property with respect to the ninth organic compound. The substance having an acceptor property is particularly preferably an organic compound having at least one of a halogen group and a cyano group, further preferably an organic compound having at least one of fluorine and a cyano group. Note that it is further preferable that the total number of halogen groups (fluorines) and cyano groups of the organic compound be four or more.

[0223] In the case where the second layer includes the ninth organic compound and the substance exhibiting an acceptor property with respect to the ninth organic compound, holes are generated by charge separation, and the holes are injected into the light-emitting unit on the cathode side through the ninth organic compound when voltage is applied between the anode and the cathode. Thus, the light-emitting device of one embodiment of the present invention can have a low driving voltage.

[0224] The intermediate layer may include a third layer between the first layer and the second layer.

[0225] The third layer includes a substance having an electron-transport property and has functions of smoothly transferring and receiving electrons between the first layer and the second layer to reduce the driving voltage, and reducing the interaction between the first layer and the second layer to improve the reliability, for example.

[0226] The thickness of the third layer is preferably greater than or equal to 1 nm and less than or equal to 10 nm, further preferably greater than or equal to 2 nm and less than or equal to 5 nm, in which case an increase in driving voltage can be inhibited.

[0227] The light-emitting device of one embodiment of the present invention that has the above structure can have high current efficiency, low energy loss, and favorable characteristics. A display device of one embodiment of the present invention that includes such a light-emitting device can achieve low power consumption, high reliability, high-luminance display, and high visibility.

[0228] Next, light-emitting devices of one embodiment of the present invention will be described in detail with reference to the drawings. FIG. 1A illustrates a light-emitting device **130** of one embodiment of the present invention. The light-emitting device of one embodiment of the present invention is a tandem light-emitting device and includes an organic compound layer **103** (also referred to as an EL layer) that includes a first light-emitting unit **501** including a first light-emitting layer **113_1**, a second light-emitting unit **502** including a second light-emitting layer **113_2** and a second electron-transport layer **1142**, and an intermediate layer **116**, between a first electrode **101** including an anode and a second electrode **102** including a cathode. Note that the first light-emitting unit may include a first electron-transport layer **114_1** between the first light-emitting layer **113_1** and the intermediate layer **116**.

[0229] In the light-emitting device **130**, the second electron-transport layer **114_2** includes the first organic compound having a triazine skeleton, and the intermediate layer **116** includes the second organic compound having a phenanthroline skeleton. The second electron-transport layer **114_2** including the first organic compound having a triazine skeleton is preferably in contact with the second electrode **102** in order to reduce power consumption.

[0230] Although light-emitting devices each including one intermediate layer **116** and two light-emitting units are described as examples in this embodiment, a light-emitting device including n intermediate layer(s) (n is an integer greater than or equal to 1) and n+1 light-emitting units may be

employed. For example, the light-emitting device **130** illustrated in FIG. 1B is an example of a tandem light-emitting device with $n=2$ that includes the first light-emitting unit **501**, a first intermediate layer **116_1**, the second light-emitting unit **502**, a second intermediate layer **116_2**, and a third light-emitting unit **503**.

[0231] The first light-emitting unit **501** and the second light-emitting unit **502** may include a functional layer in addition to the above-described light-emitting and electron-transport layers. Although FIG. 1A illustrates the structure in which the first light-emitting unit **501** is provided with a hole-injection layer **111** and a first hole-transport layer **112_1** in addition to the first light-emitting layer **113_1** and the first electron-transport layer **114_1** and the second light-emitting unit **502** is provided with a second hole-transport layer **112_2** in addition to the second light-emitting layer **113_2** and the second electron-transport layer **114_2**, the structure of the organic compound layer **103** in one embodiment of the present invention is not limited thereto and any of the layers may be omitted or other layers may be added. Typical examples of the other layers include a carrier-blocking layer and an exciton-blocking layer.

[0232] The first electrode **101** includes the anode. The first electrode **101** may have a stacked-layer structure, in which case a layer in contact with the organic compound layer **103** functions as the anode. The anode is preferably formed using a metal, an alloy, a conductive compound, or a mixture thereof each having a high work function (specifically, higher than or equal to 4.0 eV), for example. Specific examples include indium oxide-tin oxide (ITO: indium tin oxide), indium oxide-tin oxide containing silicon or silicon oxide, indium oxide-zinc oxide, and indium oxide containing tungsten oxide and zinc oxide (IWZO). Films of such conductive metal oxides are usually formed by a sputtering method, but may be formed by a sol-gel method or the like. For example, a film of indium oxide-zinc oxide is formed by a sputtering method using a target in which 1 wt % to 20 wt % zinc oxide is added to indium oxide. Furthermore, a film of indium oxide containing tungsten oxide and zinc oxide (IWZO) can be formed by a sputtering method using a target in which 0.5 wt % to 5 wt % tungsten oxide and 0.1 wt % to 1 wt % zinc oxide are added to indium oxide. Alternatively, gold (Au), platinum (Pt), nickel (Ni), tungsten (W), chromium (Cr), molybdenum (Mo), iron (Fe), cobalt (Co), copper (Cu), palladium (Pd), a nitride of a metal material (e.g., titanium nitride), or the like can be used for the anode. Graphene can also be used for the anode. Note that an electrode material can be selected regardless of the work function when the composite material forming a second layer **117** in the above intermediate layer **116** is used for the layer (typically the hole-injection layer) in contact with the anode.

[0233] The hole-injection layer **111** is provided in contact with the anode and has a function of facilitating injection of holes into the organic compound layer **103** (the first light-emitting unit **501**). The hole-injection layer **111** can be formed using a phthalocyanine-based compound or a complex compound such as phthalocyanine (abbreviation: H.sub.2Pc) or copper phthalocyanine (abbreviation: CuPc), an aromatic amine compound such as 4,4'-bis[N-(4-diphenylaminophenyl)-N-phenylamino]biphenyl (abbreviation: DPAB) or 4,4'-bis(N-{4-[N-(3-methylphenyl)-N-phenylamino]phenyl}-N-phenylamino)biphenyl (abbreviation: DNTPD), or a high molecular compound such as poly(3,4-ethylenedioxythiophene)/poly(styrenesulfonic acid) (abbreviation: PEDOT/PSS), for example.

[0234] The hole-injection layer **111** may be formed using a substance having an electron-acceptor property. Examples of the substance having an acceptor property include organic compounds having an electron-withdrawing group (e.g., a halogen group or a cyano group), such as 7,7,8,8-tetracyano-2,3,5,6-tetrafluoroquinodimethane (abbreviation: F4-TCNQ), chloranil, 2,3,6,7,10,11-hexacyano-1,4,5,8,9,12-hexaazatriphenylene (abbreviation: HAT-CN), 1,3,4,5,7,8-hexafluorotetracyano-naphthoquinodimethane (abbreviation: F6-TCNNQ), and 2-(7-dicyanomethylene-1,3,4,5,6,8,9,10-octafluoro-7H-pyren-2-ylidene)malononitrile. A compound in which electron-withdrawing groups are bonded to a condensed aromatic ring having a plurality of heteroatoms, such as HAT-CN, is particularly preferable because it is thermally stable. A

[0235] radialene derivative having an electron-withdrawing group (in particular, a cyano group, a halogen group such as a fluoro group, or the like) has a significantly high electron-acceptor property and thus is preferable. Specific examples include α,α',α'' -1,2,3-cyclopropanetriylidenetris[4-cyano-2,3,5,6-tetrafluorobenzeneacetonitrile], α,α',α'' -1,2,3-cyclopropanetriylidenetris[2,6-dichloro-3,5-difluoro-4-(trifluoromethyl)benzeneacetonitrile], and α,α',α'' -1,2,3-cyclopropanetriylidenetris[2,3,4,5,6-pentafluorobenzeneacetonitrile]. As the substance having an acceptor property, a transition metal oxide such as molybdenum oxide, vanadium oxide, ruthenium oxide, tungsten oxide, or manganese oxide can be used, other than the above-described organic compounds. Alternatively, the hole-injection layer **111** can be formed using a phthalocyanine-based compound or a complex compound such as phthalocyanine (abbreviation: H.sub.2Pc) or copper phthalocyanine (abbreviation: CuPc), an aromatic amine compound such as 4,4'-bis[N-(4-diphenylaminophenyl)-N-phenylamino]biphenyl (abbreviation: DPAB) or 4,4'-bis(N-{4-[N-(3-methylphenyl)-N-phenylamino]phenyl}-N-phenylamino)biphenyl (abbreviation: DNTPD), or a high molecular compound such as poly(3,4-ethylenedioxythiophene)/poly(styrenesulfonic acid) (abbreviation: PEDOT/PSS), for example. The substance having an acceptor property can extract electrons from an adjacent hole-transport layer (or hole-transport material) by application of an electric field.

[0236] The hole-injection layer **111** is preferably formed using a composite material containing any of the aforementioned materials having an acceptor property and a substance having a hole-transport property.

[0237] As the substance having a hole-transport property used in the composite material, any of a variety of organic compounds such as aromatic amine compounds, heteroaromatic compounds, aromatic hydrocarbons, and high molecular compounds (e.g., oligomers, dendrimers, and polymers) can be used. Note that the substance having a hole-transport property used for the composite material preferably has a hole mobility higher than or equal to 1×10^{-6} cm²/Vs. The substance having a hole-transport property used in the composite material is preferably a compound having a condensed aromatic hydrocarbon ring or a π -electron rich heteroaromatic ring. As the condensed aromatic hydrocarbon ring, an anthracene ring, a naphthalene ring, or the like is preferable. As the π -electron rich heteroaromatic ring, a condensed aromatic ring having at least one of a pyrrole skeleton, a furan skeleton, and a thiophene skeleton in the ring is preferable; specifically, a carbazole ring, a dibenzothiophene ring, or a ring in which an aromatic ring or a heteroaromatic ring is further condensed to a carbazole ring or a dibenzothiophene ring is preferable.

[0238] Such a substance having a hole-transport property further preferably has any of a carbazole skeleton, a dibenzofuran skeleton, a dibenzothiophene skeleton, and an anthracene skeleton. In particular, an aromatic amine having a substituent that has a dibenzofuran ring or a dibenzothiophene ring, an aromatic monoamine that has a naphthalene ring, or an aromatic monoamine in which a 9-fluorenyl group is bonded to nitrogen of an amine through an arylene group may be used. Note that the substance having a hole-transport property preferably has an N,N-bis(4-biphenyl)amino group to enable fabricating a light-emitting device having a long lifetime.

[0239] Specific examples of the substance having a hole-transport property include N-(4-biphenyl)-6,N-diphenylbenzo[b]naphtho[1,2-d]furan-8-amine (abbreviation: BnfABP), NN-bis(4-biphenyl)-6-phenylbenzo[b]naphtho[1,2-d]furan-8-amine (abbreviation: BBABnf), 4,4'-bis(6-phenylbenzo[b]naphtho[1,2-d]furan-8-yl)-4''-phenyltriphenylamine (abbreviation: BnfBB1BP), N,N-bis(4-biphenyl)benzo[b]naphtho[1,2-d]furan-6-amine (abbreviation: BBABnf(6)), N,N-bis(4-biphenyl)benzo[b]naphtho[1,2-d]furan-8-amine (abbreviation: BBABnf(8)), N,N-bis(4-biphenyl)benzo[b]naphtho[2,3-d]furan-4-amine (abbreviation: BBABnf(II)(4)), N,N-bis[4-(dibenzofuran-4-yl)phenyl]-4-amino-p-terphenyl (abbreviation: DBfBB1TP), N-[4-(dibenzothiophen-4-yl)phenyl]-N-phenyl-4-biphenylamine (abbreviation: ThBA1BP), 4-(2-

naphthyl)-4',4''-diphenyltriphenylamine (abbreviation: BBAPNB), 4-[4-(2-naphthyl)phenyl]-4',4''-diphenyltriphenylamine (abbreviation: BBAPNBi), 4,4'-diphenyl-4''-(6;1'-binaphthyl-2-yl)triphenylamine (abbreviation: BBAA(NPNB)), 4,4'-diphenyl-4''-(7;1'-binaphthyl-2-yl)triphenylamine (abbreviation: BBAA(NPNB-03)), 4,4'-diphenyl-4''-(7-phenyl)naphthyl-2-yltriphenylamine (abbreviation: BBAPPNB-03), 4,4'-diphenyl-4''-(6;2'-binaphthyl-2-yl)triphenylamine (abbreviation: BBA(PN2)B), 4,4'-diphenyl-4''-(7;2'-binaphthyl-2-yl)triphenylamine (abbreviation: BBA(PN2)B-03), 4,4'-diphenyl-4''-(4;2'-binaphthyl-1-yl)triphenylamine (abbreviation: BBAPNaNB), 4,4'-diphenyl-4''-(5;2'-binaphthyl-1-yl)triphenylamine (abbreviation: BBAPNaNB-02), 4-(4-biphenyl)-4'-[4-(2-naphthyl)-4''-phenyltriphenylamine (abbreviation: TPBiAPNB), 4-(3-biphenyl)-4'-[4-(2-naphthyl)phenyl]-4''-phenyltriphenylamine (abbreviation: mTPBiAPNBi), 4-(4-biphenyl)-4'-[4-(2-naphthyl)phenyl]-4''-phenyltriphenylamine (abbreviation: TPBiAPNBi), 4-phenyl-4'-(1-naphthyl)triphenylamine (abbreviation: aNBA1BP), 4,4'-bis(1-naphthyl)triphenylamine (abbreviation: aNBB1BP), 4,4'-diphenyl-4''-[4'-(carbazol-9-yl)biphenyl-4-yl]triphenylamine (abbreviation: YGTBi1BP), 4'-[4-(3-phenyl-9H-carbazol-9-yl)phenyl]tris(biphenyl-4-yl)amine (abbreviation: YGTBi1BP-02), 4-[4'-(carbazol-9-yl)biphenyl-4-yl]-4''-(2-naphthyl)-4''-phenyltriphenylamine (abbreviation: YGTBiPNB), N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-N-[4-(1-naphthyl)phenyl]-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: PCBNBSF), N,N-bis(biphenyl-4-yl)-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: BBASF), N,N-bis(biphenyl-4-yl)-9,9'-spirobi[9H-fluoren]-4-amine (abbreviation: BBASF(4)), N-(biphenyl-2-yl)-N-(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi[9H-fluoren]-4-amine (abbreviation: oFBiSF), N-(biphenyl-4-yl)-N-(9,9-dimethyl-9H-fluoren-2-yl)dibenzofuran-4-amine (abbreviation: FrBiF), N-[4-(1-naphthyl)phenyl]-N-[3-(6-phenyldibenzofuran-4-yl)phenyl]-1-naphthylamine (abbreviation: mPDBfBNBN), 4-phenyl-4'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: BPAFLP), 4-phenyl-3'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: mBPAFLP), 4-phenyl-4'-[4-(9-phenylfluoren-9-yl)phenyl]triphenylamine (abbreviation: BPAFLBi), 4-phenyl-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBA1BP), 4,4'-diphenyl-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBBi1BP), 4-(1-naphthyl)-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBANB), 4,4'-di(1-naphthyl)-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBNBB), N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: PCBASF), N-(biphenyl-4-yl)-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9-dimethyl-9H-fluoren-2-amine (abbreviation: PCBBiF), N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-4-amine, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-3-amine, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-2-amine, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-1-amine, 9-[3-(triphenylsilyl)phenyl]-3,9'-bi-9H-carbazole (abbreviation: PSiCzCz), and 9'-[3-(triphenylsilyl)phenyl]-9'H-9,3':6',9''-tercarbazole (abbreviation: PSiCzGI).

[0240] Examples of the aromatic amine compounds that can be used as the substance having a hole-transport property include N,N-di(p-tolyl)-N,N-diphenyl-p-phenylenediamine (abbreviation: DTDPPA), 4,4'-bis[N-(4-diphenylaminophenyl)-N-phenylamino]biphenyl (abbreviation: DPAB), 4,4'-bis(N-{4-[N-(3-methylphenyl)-N-phenylamino]phenyl}-N-phenylamino)biphenyl (abbreviation: DNTPD), and 1,3,5-tris[N-(4-diphenylaminophenyl)-N-phenylamino]benzene (abbreviation: DPA3B).

[0241] The formation of the hole-injection layer **111** can improve the hole-injection property, which allows the light-emitting device to be driven at a low voltage.

[0242] Among substances having an acceptor property, an organic compound having an acceptor property is easy to use because the organic compound is easily deposited by evaporation as a film.

[0243] The hole-transport layer (the first hole-transport layer **112_1** or the second hole-transport layer **112_2**) includes an organic compound having a hole-transport property. The organic compound having a hole-transport property preferably has a hole mobility higher than or equal to

1×10.sup.-6 cm.sup.2/Vs.

[0244] Examples of the aforementioned organic compound having a hole-transport property include the following compounds: compounds having an aromatic amine skeleton, such as 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (abbreviation: NPB), N,N'-diphenyl-N,N-bis(3-methylphenyl)-4,4'-diaminobiphenyl (abbreviation: TPD), N,N-bis(9,9'-spirobi[9H-fluoren]-2-yl)-N,N-diphenyl-4,4'-diaminobiphenyl (abbreviation: BSPB), 4-phenyl-4'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: BPAFLP), 4-phenyl-3'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: mBPAFLP), 4-phenyl-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBA1BP), 4,4'-diphenyl-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBBi1BP), 4-(1-naphthyl)-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBANB), 4,4'-di(1-naphthyl)-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBNNB), 9,9-dimethyl-N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]fluoren-2-amine (abbreviation: PCBAF), and N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: PCBASF); compounds having a carbazole skeleton, such as 1,3-bis(N-carbazolyl)benzene (abbreviation: mCP), 4,4'-di(N-carbazolyl)biphenyl (abbreviation: CBP), 3,6-bis(3,5-diphenylphenyl)-9-phenylcarbazole (abbreviation: CzTP), 3,3'-bis(9-phenyl-9H-carbazole) (abbreviation: PCCP), 9,9'-bis(biphenyl-4-yl)-3,3'-bi-9H-carbazole (abbreviation: BisBPCz), 9,9'-bis(biphenyl-3-yl)-3,3'-bi-9H-carbazole (abbreviation: BismBPCz), 9-(biphenyl-3-yl)-9'-(biphenyl-4-yl)-9H,9'H-3,3'-bicarbazole (abbreviation: mBPCCBP), 9-(2-naphthyl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: β NCCP), 9-(3-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCmBP), 9-(4-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCBP), 9,9'-di-2-naphthyl-3,3'-9H,9'H-bicarbazole (abbreviation: BisPNCz), 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-5'-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-phenyl-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole (abbreviation: PCCzTp), 9,9'-bis(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(4-biphenyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(triphenylen-2-yl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-1-amine, and 9-[3-(triphenylsilyl)phenyl]-3,9'-bi-9H-carbazole (abbreviation: PSiCzCz); compounds having a thiophene skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzothiophene) (abbreviation: DBT3P-II), 2,8-diphenyl-4-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]dibenzothiophene (abbreviation: DBTFLP-III), and 4-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]-6-phenyldibenzothiophene (abbreviation: DBTFLP-IV); and compounds having a furan skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzofuran) (abbreviation: DBF3P-II) and 4-{3-[3-(9-phenyl-9H-fluoren-9-yl)phenyl]phenyl}dibenzofuran (abbreviation: mmDBFFLBi-II). Among the above compounds, the compound having an aromatic amine skeleton and the compound having a carbazole skeleton are preferable because these compounds are highly reliable and have a high hole-transport property to contribute to a reduction in driving voltage. Any of the organic compounds given as examples of the substance having a hole-transport property that is used for the composite material in the hole-injection layer **111** can also be suitably used as the material included in the hole-transport layer **112**. Note that any of the above organic compounds deuterated as appropriate can also be used.

[0245] Note that the first hole-transport layer **112_1** and the second hole-transport layer **112_2** preferably include organic compounds having the same skeleton, and further preferably include the same compound. One or both of the first hole-transport layer **112_1** and the second hole-transport layer **112_2** may have a stacked-layer structure. When the hole-transport layer **112** has a stacked-layer structure and the layer closer to the light-emitting layer **113** includes an organic compound having high electron tolerance and/or an organic compound having an electron-blocking property, the light-emitting device can have high reliability. In the case where the hole-transport layer **112**

has a stacked-layer structure, a material having an excellent hole-transport property, a low electron-transport property, and a high LUMO level is preferably used for the layer closer to the light-emitting layer **113**. The LUMO level of the material is preferably higher than that of a material having the highest constituent ratio among the materials included in the light-emitting layer or a material having the highest LUMO level among the materials included in the light-emitting layer, further preferably by 0.30 eV or more. The material is preferably an organic compound having an amine skeleton and a polycyclic heteroaromatic ring, further preferably an organic compound having an amine skeleton and a furan skeleton or a dibenzofuran skeleton. In the case where the hole-transport layer **112** has a stacked-layer structure, using the above-described material for the layer closer to the light-emitting layer **113** prevents the passing of electrons from the light-emitting layer **113** to the first electrode **101** side, so that a display device with high efficiency and a long lifetime can be manufactured. Note that in the hole-transport layer **112** having a stacked-layer structure, an organic compound having an amine skeleton and a polycyclic hydrocarbon is preferably used for the layer closer to the first electrode **101**, and an organic compound having an amine skeleton and a fluorene skeleton is further preferably used for the layer. It is preferable to use the organic compound having an amine skeleton and a fluorene skeleton because the organic compound has high reliability and a high hole-transport property, which leads to the reduction of power consumption of the light-emitting device.

[0246] The light-emitting layers (the first light-emitting layer **113_1** and the second light-emitting layer **113_2**) each preferably include an emission center substance and a host material. At least one of the light-emitting layers has a structure in which the emission center substance, the first host material, and the second host material are included, the first host material and the second host material are both organic compounds, and one or both of the first host material and the second host material are deuterated. The first host material and the second host material preferably form an exciplex in combination. Note that both the first light-emitting layer **113_1** and the second light-emitting layer **113_2** preferably have such a structure. The light-emitting layers may additionally include another material.

[0247] The first light-emitting layer **113_1** and the second light-emitting layer **113_2** preferably emit light of similar colors. For example, red, green, and blue pixels are often used in a full-color display device. In a light-emitting device used in a red pixel, both the first light-emitting layer **113_1** and the second light-emitting layer **113_2** emit red light. In a green pixel, both of the two light-emitting layers emit green light. In a blue pixel, both of the two light-emitting layers emit blue light. In that case, the difference in maximum peak wavelength between the emission spectrum of the compound as the emission center substance of the first light-emitting layer **113_1** and the emission spectrum of the compound as the emission center substance of the second light-emitting layer **113_2** is preferably less than or equal to 30 nm, further preferably less than or equal to 20 nm, still further preferably less than or equal to 10 nm. Note that it is further preferable that the first light-emitting layer **113_1** and the second light-emitting layer **113_2** include the same emission center substance. It is still further preferable that the first light-emitting layer **113_1** and the second light-emitting layer **113_2** be made of the same material.

[0248] The emission center substance may be a fluorescent substance, a phosphorescent substance, a substance exhibiting thermally activated delayed fluorescence (TADF), or any other light-emitting substance.

[0249] Examples of the fluorescent substance that can be used as the emission center substance in the light-emitting layer are as follows. Other fluorescent substances can also be used.

[0250] The examples include 5,6-bis[4-(10-phenyl-9-anthryl)phenyl]-2,2'-bipyridine (abbreviation: PAP2BPy), 5,6-bis[4'-(10-phenyl-9-anthryl)biphenyl-4-yl]-2,2'-bipyridine (abbreviation: PAPP2BPy), N,N-diphenyl-N,N-bis[4-(9-phenyl-9H-fluoren-9-yl)phenyl]pyrene-1,6-diamine (abbreviation: 1,6FLPAPrn), N,N-bis(3-methylphenyl)-N,N-bis[3-(9-phenyl-9H-fluoren-9-yl)phenyl]pyrene-1,6-diamine (abbreviation: 1,6mMemFLPAPrn), N,N-bis[4-(9H-carbazol-9-

yl)phenyl]-N,N-diphenylstilbene-4,4'-diamine (abbreviation: YGA2S), 4-(9H-carbazol-9-yl)-4'-(10-phenyl-9-anthryl)triphenylamine (abbreviation: YGAPA), 4-(9H-carbazol-9-yl)-4'-(9,10-diphenyl-2-anthryl)triphenylamine (abbreviation: 2YGAPPA), N,9-diphenyl-N-[4-(10-phenyl-9-anthryl)phenyl]-9H-carbazol-3-amine (abbreviation: PCAPA), perylene, 2,5,8,11-tetra-tert-butylperylene (abbreviation: TBP), 4-(10-phenyl-9-anthryl)-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBAPA), N,N'-(2-tert-butylanthracene-9,10-diyl)-4,1-phenylene)bis(N,N,N-triphenyl-1,4-phenylenediamine) (abbreviation: DPABPA), N,9-diphenyl-N-[4-(9,10-diphenyl-2-anthryl)phenyl]-9H-carbazol-3-amine (abbreviation: 2PCAPPA), N-[4-(9,10-diphenyl-2-anthryl)phenyl]-N,N,N-triphenyl-1,4-phenylenediamine (abbreviation: 2DPAPPA), N,N,N,N,N',N',N'',N''-octaphenyldibenzo[g,p]chrysene-2,7,10,15-tetraamine (abbreviation: DBC1), coumarin 30, N-(9,10-diphenyl-2-anthryl)-N,9-diphenyl-9H-carbazol-3-amine (abbreviation: 2PCAPA), N-[9,10-bis(biphenyl-2-yl)-2-anthryl]-N,9-diphenyl-9H-carbazol-3-amine (abbreviation: 2PCABPhA), N-(9,10-diphenyl-2-anthryl)-N,N,N-triphenyl-1,4-phenylenediamine (abbreviation: 2DPAPA), N-[9,10-bis(biphenyl-2-yl)-2-anthryl]-N,N,N-triphenyl-1,4-phenylenediamine (abbreviation: 2DPABPhA), 9,10-bis(biphenyl-2-yl)-N-[4-(9H-carbazol-9-yl)phenyl]-N-phenylanthracen-2-amine (abbreviation: 2YGABPhA), N,N,9-triphenylanthracen-9-amine (abbreviation: DPhAPhA), coumarin 545T, N,N-diphenylquinacridone (abbreviation: DPQd), rubrene, 5,12-bis(biphenyl-4-yl)-6,11-diphenyltetracene (abbreviation: BPT), 2-(2-{2-[4-(dimethylamino)phenyl]ethenyl}-6-methyl-4H-pyran-4-ylidene)propanedinitrile (abbreviation: DCM1), 2-{2-methyl-6-[2-(2,3,6,7-tetrahydro-1H,5H-benzo[ij]quinolizin-9-yl)ethenyl]-4H-pyran-4-ylidene}propanedinitrile (abbreviation: DCM2), N,N,N,N-tetrakis(4-methylphenyl)tetracene-5,11-diamine (abbreviation: p-mPhTD), 7,14-diphenyl-N,N,N,N-tetrakis(4-methylphenyl)acenaphtho[1,2-a]fluoranthene-3,10-diamine (abbreviation: p-mPhAFD), 2-{2-isopropyl-6-[2-(1,1,7,7-tetramethyl-2,3,6,7-tetrahydro-1H,5H-benzo[ij]quinolizin-9-yl)ethenyl]-4H-pyran-4-ylidene}propanedinitrile (abbreviation: DCJTI), 2-{2-tert-butyl-6-[2-(1,1,7,7-tetramethyl-2,3,6,7-tetrahydro-1H,5H-benzo[ij]quinolizin-9-yl)ethenyl]-4H-pyran-4-ylidene}propanedinitrile (abbreviation: DCJTB), 2-(2,6-bis{2-[4-(dimethylamino)phenyl]ethenyl}-4H-pyran-4-ylidene)propanedinitrile (abbreviation: BisDCM), 2-{2,6-bis[2-(8-methoxy-1,1,7,7-tetramethyl-2,3,6,7-tetrahydro-1H,5H-benzo[ij]quinolizin-9-yl)ethenyl]-4H-pyran-4-ylidene}propanedinitrile (abbreviation: BisDCJTM), N,N-diphenyl-N,N'-(1,6-pyrene-diyl)bis[(6-phenylbenzo[b]naphtho[1,2-d]furan)-8-amine] (abbreviation: 1,6BnfAPrn-03), N,N-diphenyl-N,N-bis(9-phenyl-9H-carbazol-2-yl)naphtho[2,3-b;6,7-b']bisbenzofuran-3,10-diamine (abbreviation: 3,10PCA2Nbf(IV)-02), and 3,10-bis[N-(dibenzofuran-3-yl)-N-phenylamino]naphtho[2,3-b;6,7-b']bisbenzofuran (abbreviation: 3,10FrA2Nbf(IV)-02). Condensed aromatic diamine compounds typified by pyrenediamine compounds such as 1,6FLPAPrn, 1,6mMemFLPAPrn, and 1,6BnfAPrn-03 are particularly preferable because of their high hole-trapping properties, high emission efficiency, or high reliability.

[0251] A preferable phosphorescent substance that can be used as the emission center substance in the light-emitting layer is a metal complex, in particular, an iridium complex or a platinum complex, examples of which are as follows.

[0252] The examples include organometallic iridium complexes having a 4H-triazole skeleton, such as tris{2-[5-(2-methylphenyl)-4-(2,6-dimethylphenyl)-4H-1,2,4-triazol-3-yl-κN.sup.2]phenyl-κC}iridium(III) (abbreviation: [Ir(mpptz-dmp).sub.3]), and tris(5-methyl-3,4-diphenyl-4H-1,2,4-triazolato)iridium(III) (abbreviation: [Ir(Mptz).sub.3]); organometallic iridium complexes having a 1H-triazole skeleton, such as tris[3-methyl-1-(2-methylphenyl)-5-phenyl-1H-1,2,4-triazolato]iridium(III) (abbreviation: [Ir(Mptz1-mp).sub.3]) and tris(1-methyl-5-phenyl-3-propyl-1H-1,2,4-triazolato)iridium(III) (abbreviation: [Ir(Prptz1-Me).sub.3]); organometallic iridium complexes having an imidazole skeleton, such as fac-tris[l-(2,6-diisopropylphenyl)-2-phenyl-1H-imidazole]iridium(III) (abbreviation: [Ir(iPrpim).sub.3]), tris[3-(2,6-dimethylphenyl)-7-methylimidazo[1,2-f]phenanthridinato]iridium(III) (abbreviation: [Ir(dmpimpt-Me).sub.3]), and

tris(2-{1-[2,6-bis(1-methylethyl)phenyl]-1H-imidazol-2-yl-κN.sup.3}-4-cyanophenyl-κC)iridium(III) (abbreviation: CNImIr); organometallic complexes having a benzimidazolidene skeleton, such as tris[(6-tert-butyl-3-phenyl-2H-imidazo[4,5-b]pyrazin-1-yl-κC.sup.2)phenyl-κC]iridium(III) (abbreviation: [Ir(cb).sub.3]); organometallic iridium complexes in which a phenylpyridine derivative having an electron-withdrawing group is a ligand, such as bis[2-(4',6'-difluorophenyl)pyridinato-N,C.sup.2']iridium(III) tetrakis(1-pyrazolyl)borate (abbreviation: FIr6), bis[2-(4',6'-difluorophenyl)pyridinato-N,C.sup.2']iridium(III) picolinate (abbreviation: FIrpic), bis{2-[3',5'-bis(trifluoromethyl)phenyl]pyridinato-N,C.sup.2'}iridium(III) picolinate (abbreviation: [Ir(CF.sub.3ppy).sub.2(pic)]), and bis[2-(4',6'-difluorophenyl)pyridinato-N,C.sup.2']iridium(III) acetylacetonate (abbreviation: FIracac); and platinum complexes such as (2-{3-[3-(3,5-di-tert-butylphenyl)benzimidazol-1-yl-2-ylidene-κC.sup.2]phenoxy-κC.sup.2}-9-(4-tert-butyl-2-pyridinyl-κNA)carbazole-2,1-diyl-κC.sup.1)platinum(II) (abbreviation: PtON-TBBI). These compounds emit blue-hued phosphorescent light and have an emission peak in the wavelength range from 450 nm to 520 nm. Alternatively, a compound obtained by substituting deuterium for part of hydrogen in any of these compounds can also be used.

[0253] Other examples include organometallic iridium complexes having a pyrimidine skeleton, such as tris(4-methyl-6-phenylpyrimidinato)iridium(III) (abbreviation: [Ir(mppm).sub.3]), tris(4-tert-butyl-6-phenylpyrimidinato)iridium(III) (abbreviation: [Ir(tBuppm).sub.3]), (acetylacetonato)bis(6-methyl-4-phenylpyrimidinato)iridium(III) (abbreviation: [Ir(mppm).sub.2(acac)]), (acetylacetonato)bis(6-tert-butyl-4-phenylpyrimidinato)iridium(III) (abbreviation: [Ir(tBuppm)2(acac)]), (acetylacetonato)bis[6-(2-norbornyl)-4-phenylpyrimidinato]iridium(III) (abbreviation: [Ir(nbppm).sub.2(acac)]), (acetylacetonato)bis[5-methyl-6-(2-methylphenyl)-4-phenylpyrimidinato]iridium(III) (abbreviation: [Ir(mppm).sub.2(acac)]), and (acetylacetonato)bis(4,6-diphenylpyrimidinato)iridium(III) (abbreviation: [Ir(dppm).sub.2(acac)]); organometallic iridium complexes having a pyrazine skeleton, such as (acetylacetonato)bis(3,5-dimethyl-2-phenylpyrazinato)iridium(III) (abbreviation: [Ir(mppr-Me).sub.2(acac)]) and (acetylacetonato)bis(5-isopropyl-3-methyl-2-phenylpyrazinato)iridium(III) (abbreviation: [Ir(mppr-iPr).sub.2(acac)]); organometallic iridium complexes having a pyridine skeleton, such as tris(2-phenylpyridinato-N,C.sup.2')iridium(III) (abbreviation: [Ir(ppy).sub.3]), bis(2-phenylpyridinato-N,C.sup.2')iridium(III) acetylacetonate (abbreviation: [Ir(ppy).sub.2(acac)]), bis(benzo[h]quinolinato)iridium(III) acetylacetonate (abbreviation: [Ir(bzq).sub.2(acac)]), tris(benzo[h]quinolinato)iridium(III) (abbreviation: [Ir(bzq).sub.3]), tris(2-phenylquinolinato-N,C.sup.2')iridium(III) (abbreviation: [Ir(pq).sub.3]), bis(2-phenylquinolinato-N,C.sup.2')iridium(III) acetylacetonate (abbreviation: [Ir(pq).sub.2(acac)]), [2-d.sub.3-methyl-8-(2-pyridinyl-κN)benzofuro[2,3-b]pyridine-κC]bis[2-(5-d.sub.3-methyl-2-pyridinyl-κN.sup.2)phenyl-κC]iridium(III) (abbreviation: Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3)), {2-(methyl-d.sub.3)-8-[4-(1-methylethyl-1-d)-2-pyridinyl-N]benzofuro[2,3-b]pyridin-7-yl-κC}bis{5-(methyl-d.sub.3)-2-[5-(methyl-d.sub.3)-2-pyridinyl-κN]phenyl-κC}iridium(III) (abbreviation: Ir(5mtpy-d.sub.6).sub.2(mbfppy-iPr-d.sub.4)), [2-d.sub.3-methyl-(2-pyridinyl-κN)benzofuro[2,3-b]pyridine-κC]bis[2-(2-pyridinyl-κN)phenyl-κC]iridium(III) (abbreviation: Ir(ppy).sub.2(mbfppy-d.sub.3)), [2-(4-methyl-5-phenyl-2-pyridinyl-κN)phenyl-κC]bis[2-(2-pyridinyl-κN)phenyl-κC]iridium(III) (abbreviation: Ir(ppy).sub.2(mdppy)), [2-(4-d.sub.3-methyl-5-phenyl-2-pyridinyl-κN.sup.2)phenyl-κC]bis[2-(5-d.sub.3-methyl-2-pyridinyl-κN.sup.2)phenyl-κC]iridium(III) (abbreviation: [Ir(5mppy-d.sub.3).sub.2(mdppy-d.sub.3)]), [2-methyl-(2-pyridinyl-κN)benzofuro[2,3-b]pyridine-κC]bis[2-(2-pyridinyl-κN)phenyl-κC]iridium(III) (abbreviation: [Ir(ppy).sub.2(mbfppy)]), [2-(4-methyl-5-phenyl-2-pyridinyl-κN)phenyl-κC]bis[2-(2-pyridinyl-κN)phenyl-κC]iridium (abbreviation: [Ir(ppy).sub.2(mdppy)]), and tris{2-[5-(methyl-d.sub.3)-4-phenyl-2-pyridinyl-κN]phenyl-κC}iridium(III) (abbreviation: Ir(5m4dppy-d.sub.3).sub.3); organometallic platinum complexes such as (2-{1-(5-tert-butylbiphenyl-2-yl)-4-[3-tert-butyl-5-(4-phenyl-2-pyridinyl-κN)phenyl-κC.sup.6]-2-benzimidazolyl-κN.sup.3}-4,6-di-tert-butylphenolato-

κO)]platinum(II) (abbreviation: Pt(tBdppymmtBubiz-tBubp)) and [2-(4-(3,5-di-tert-butylphenyl)-6-{3-[4-(5'-tert-butyl[1,1':3',1''-terphenyl]-2'-yl)-2-pyridinyl-N]phenyl-κC.sup.2}-2-pyridinyl-κN)phenolato-κO)]platinum(II) (abbreviation: Pt(4tButppypyp-mmtBup)); and rare earth metal complexes such as tris(acetylacetonato)(monophenanthroline)terbium(III) (abbreviation: [Tb(acac).sub.3(Phen)]). These compounds mainly emit green-hued phosphorescent light and have an emission peak in the wavelength range from 500 nm to 600 nm. Note that organometallic iridium complexes having a pyrimidine skeleton have distinctively high reliability or emission efficiency and thus are particularly preferable. Alternatively, a compound obtained by substituting deuterium for part of hydrogen in any of these compounds can also be used.

[0254] Other examples include organometallic iridium complexes having a pyrimidine skeleton, such as (diisobutyrylmethanato)bis[4,6-bis(3-methylphenyl)pyrimidinato]iridium(III) (abbreviation: [Ir(5mdppm).sub.2(dibm)]), bis[4,6-bis(3-methylphenyl)pyrimidinato](dipivaloylmethanato)iridium(III) (abbreviation: [Ir(5mdppm).sub.2(dpm)]), and bis[4,6-di(naphthalen-1-yl)pyrimidinato](dipivaloylmethanato)iridium(III) (abbreviation: [Ir(d1npm).sub.2(dpm)]); organometallic iridium complexes having a pyrazine skeleton, such as (acetylacetonato)bis(2,3,5-triphenylpyrazinato)iridium(III) (abbreviation: [Ir(tppr).sub.2(acac)]), bis(2,3,5-triphenylpyrazinato)(dipivaloylmethanato)iridium(III) (abbreviation: [Ir(tppr).sub.2(dpm)]), and (acetylacetonato)bis[2,3-bis(4-fluorophenyl)quinoxalinato]iridium(III) (abbreviation: [Ir(Fdpq).sub.2(acac)]); organometallic iridium complexes having a pyridine skeleton, such as tris(1-phenylisoquinolinato-N,C.sup.2')iridium(III) (abbreviation: [Ir(piq).sub.3]), bis(1-phenylisoquinolinato-N,C.sup.2')iridium(III) acetylacetonate (abbreviation: [Ir(piq).sub.2(acac)]), (3,7-diethyl-4,6-nonanedionato-κO.sup.4,κO.sup.6)bis[2,4-dimethyl-6-[7-(1-methylethyl)-1-isoquinoliny-N]phenyl-κC]iridium(III), and (3,7-diethyl-4,6-nonanedionato-κO.sup.4,κO.sup.6)bis[2,4-dimethyl-6-[5-(1-methylethyl)-2-quinoliny-N]phenyl-κC]iridium(III); platinum complexes such as 2,3,7,8,12,13,17,18-octaethyl-21H,23H-porphyrinplatinum(II) (abbreviation: PtOEP); and rare earth metal complexes such as tris(1,3-diphenyl-1,3-propanedionato)(monophenanthroline)europium(III) (abbreviation: [Eu(DBM).sub.3(Phen)] and tris[1-(2-thenoyl)-3,3,3-trifluoroacetato](monophenanthroline)europium(III) (abbreviation: [Eu(TTA).sub.3(Phen)]). These compounds emit red-hued phosphorescent light and have an emission peak in the wavelength range from 600 nm to 700 nm. Furthermore, the organometallic iridium complexes having a pyrazine skeleton can provide red light emission with favorable chromaticity. Alternatively, a compound obtained by substituting deuterium for part of hydrogen in any of these compounds can also be used.

[0255] Note that in one embodiment of the present invention, the use of a deuterated compound as the emission center substance improves the emission efficiency. Thus, the emission center substance is preferably a deuterated material.

[0256] Besides the above phosphorescent compounds, known phosphorescent compounds may be selected and used.

[0257] Examples of the TADF material include a fullerene, a derivative thereof, an acridine, a derivative thereof, and an eosin derivative. Furthermore, a metal-containing porphyrin, such as a porphyrin containing magnesium (Mg), zinc (Zn), cadmium (Cd), tin (Sn), platinum (Pt), indium (In), or palladium (Pd), can be given. Examples of the metal-containing porphyrin include a protoporphyrin-tin fluoride complex (SnF.sub.2(Proto IX)), a mesoporphyrin-tin fluoride complex (SnF.sub.2(Meso IX)), a hematoporphyrin-tin fluoride complex (SnF.sub.2(Hemato IX)), a coproporphyrin tetramethyl ester-tin fluoride complex (SnF.sub.2(Copro III-4Me)), an octaethylporphyrin-tin fluoride complex (SnF.sub.2(OEP)), an etioporphyrin-tin fluoride complex (SnF.sub.2(Etio I)), and an octaethylporphyrin-platinum chloride complex (PtCl.sub.2OEP), which are represented by the following structural formulae.

##STR00006## ##STR00007## ##STR00008##

[0258] Alternatively, it is possible to use a heterocyclic compound having one or both of a π-

electron rich heteroaromatic ring and a π -electron deficient heteroaromatic ring that is represented by any of the following structural formulae, such as 2-(biphenyl-4-yl)-4,6-bis(12-phenylindolo[2,3-a]carbazol-11-yl)-1,3,5-triazine (abbreviation: PIC-TRZ), 9-(4,6-diphenyl-1,3,5-triazin-2-yl)-9'-phenyl-9H,9'H-3,3'-bicarbazole (abbreviation: PCCzTzn), 2-{4-[3-(N-phenyl-9H-carbazol-3-yl)-9H-carbazol-9-yl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: PCCzPTzn), 2-[4-(10H-phenoxazin-10-yl)phenyl]-4,6-diphenyl-1,3,5-triazine (abbreviation: PXZ-TRZ), 3-[4-(5-phenyl-5,10-dihydrophenazin-10-yl)phenyl]-4,5-diphenyl-1,2,4-triazole (abbreviation: PPZ-3TPT), 3-(9,9-dimethyl-9H-acridin-10-yl)-9H-xanthen-9-one (abbreviation: ACRXTN), bis[4-(9,9-dimethyl-9,10-dihydroacridine)phenyl]sulfone (abbreviation: DMAC-DPS), or 10-phenyl-10H,10'H-spiro[acridin-9,9'-anthracen]-10'-one (abbreviation: ACRSA). Such a heterocyclic compound is preferable because of having high electron-transport and hole-transport properties owing to a π -electron rich heteroaromatic ring and a π -electron deficient heteroaromatic ring. Among skeletons having the π -electron deficient heteroaromatic ring, a pyridine skeleton, a diazine skeleton (a pyrimidine skeleton, a pyrazine skeleton, and a pyridazine skeleton), and a triazine skeleton are preferable because of their high stability and reliability. In particular, a benzofuopyrimidine skeleton, a benzothienopyrimidine skeleton, a benzofuopyrazine skeleton, and a benzothienopyrazine skeleton are preferable because of their high acceptor properties and high reliability. Among skeletons having the π -electron rich heteroaromatic ring, an acridine skeleton, a phenoxazine skeleton, a phenothiazine skeleton, a furan skeleton, a thiophene skeleton, and a pyrrole skeleton have high stability and reliability; thus, at least one of these skeletons is preferably included. A dibenzofuran skeleton is preferable as a furan skeleton, and a dibenzothiophene skeleton is preferable as a thiophene skeleton. As a pyrrole skeleton, an indole skeleton, a carbazole skeleton, an indolocarbazole skeleton, a bicarbazole skeleton, and a 3-(9-phenyl-9H-carbazol-3-yl)-9H-carbazole skeleton are particularly preferable. Note that a substance in which the π -electron rich heteroaromatic ring is directly bonded to the π -electron deficient heteroaromatic ring is particularly preferable because the electron-donating property of the π -electron rich heteroaromatic ring and the electron-acceptor property of the π -electron deficient heteroaromatic ring are both improved, the energy difference between the Si level and the T.sub.1 level becomes small, and thus thermally activated delayed fluorescence can be obtained with high efficiency. Note that an aromatic ring to which an electron-withdrawing group such as a cyano group is bonded may be used instead of the π -electron deficient heteroaromatic ring. As a π -electron rich skeleton, an aromatic amine skeleton, a phenazine skeleton, or the like can be used. As a π -electron deficient skeleton, a xanthene skeleton, a thioxanthene dioxide skeleton, an oxadiazole skeleton, a triazole skeleton, an imidazole skeleton, an anthraquinone skeleton, a skeleton including boron such as phenylborane or boranthrene, an aromatic ring or a heteroaromatic ring having a cyano group or a nitrile group such as benzonitrile or cyanobenzene, a carbonyl skeleton such as benzophenone, a phosphine oxide skeleton, a sulfone skeleton, or the like can be used. As described above, a π -electron deficient skeleton and a π -electron rich skeleton can be used instead of at least one of the π -electron deficient heteroaromatic ring and the π -electron rich heteroaromatic ring.

##STR00009## ##STR00010## ##STR00011##

[0259] Alternatively, a TADF material whose singlet excited state and triplet excited state are in a thermal equilibrium state may be used. Since such a TADF material enables a short emission lifetime (excitation lifetime), the efficiency of a light-emitting device in a high-luminance region can be less likely to decrease. Specifically, a material having the following molecular structure can be used.

##STR00012##

[0260] Note that a TADF material is a material having a small difference between the Si level and the T.sub.1 level and a function of converting triplet excitation energy into singlet excitation energy by reverse intersystem crossing. Thus, a TADF material can upconvert triplet excitation energy into singlet excitation energy (i.e., reverse intersystem crossing) using a small amount of thermal energy

and efficiently generate a singlet excited state. In addition, the triplet excitation energy can be converted into light emission.

[0261] An exciplex whose excited state is formed of two kinds of substances has an extremely small difference between the Si level and the T.sub.1 level and functions as a TADF material capable of converting triplet excitation energy into singlet excitation energy.

[0262] A phosphorescent spectrum observed at a low temperature (e.g., 77 K to 10 K) is used for an index of the T.sub.1 level. When the level of energy with a wavelength of the line obtained by extrapolating a tangent to the fluorescent spectrum at a tail on the shorter wavelength side is the Si level and the level of energy with a wavelength of the line obtained by extrapolating a tangent to the phosphorescent spectrum at a tail on the shorter wavelength side is the T.sub.1 level, the difference between the Si level and the T.sub.1 level of the TADF material is preferably less than or equal to 0.3 eV, further preferably less than or equal to 0.2 eV.

[0263] When a TADF material is used as a light-emitting substance, the Si level of a host material is preferably higher than that of the TADF material. In addition, the T.sub.1 level of the host material is preferably higher than that of the TADF material.

[0264] The host materials in the light-emitting layer having the structure of one embodiment of the present invention are described in detail above; thus, repeated description thereof is omitted. Since the light-emitting device of one embodiment of the present invention is a tandem light-emitting device, a plurality of light-emitting layers are included. Thus, some of the light-emitting layers might not have the above structure. In the case of a light-emitting layer not having this structure, any of a variety of carrier-transport materials such as an organic compound having an electron-transport property and/or an organic compound having a hole-transport property can be used as the host material(s).

[0265] The organic compound having a hole-transport property is preferably an organic compound having an amine skeleton or a π -electron rich heteroaromatic ring, for example. As the π -electron rich heteroaromatic ring, a condensed aromatic ring having at least one of an acridine skeleton, a phenoxazine skeleton, a phenothiazine skeleton, a furan skeleton, a thiophene skeleton, and a pyrrole skeleton in the ring is preferable; specifically, a carbazole ring, a dibenzothiophene ring, or a ring in which an aromatic ring or a heteroaromatic ring is further condensed to a carbazole ring or a dibenzothiophene ring is preferable.

[0266] Such a substance having a hole-transport property further preferably has any of a carbazole skeleton, a dibenzofuran skeleton, a dibenzothiophene skeleton, and an anthracene skeleton. In particular, an aromatic amine having a substituent that has a dibenzofuran ring or a dibenzothiophene ring, an aromatic monoamine that has a naphthalene ring, or an aromatic monoamine in which a 9-fluorenyl group is bonded to nitrogen of an amine through an arylene group may be used. Note that the substance having a hole-transport property is preferably an organic compound having an N,N-bis(4-biphenyl)amino group to enable fabricating a light-emitting device having a long lifetime.

[0267] Preferable examples of such organic compounds include the following organic compounds: compounds having an aromatic amine skeleton, such as 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (abbreviation: NPB), N,N-diphenyl-N,N-bis(3-methylphenyl)-4,4'-diaminobiphenyl (abbreviation: TPD), N,N'-bis(9,9'-spirobi[9H-fluoren]-2-yl)-N,N-diphenyl-4,4'-diaminobiphenyl (abbreviation: BSPB), 4-phenyl-4'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: BPAFLP), 4-phenyl-3'-(9-phenylfluoren-9-yl)triphenylamine (abbreviation: mBPAFLP), 4-phenyl-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBA1BP), 4,4'-diphenyl-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBBi1BP), 4-(1-naphthyl)-4'-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBANB), 4,4'-di(1-naphthyl)-4''-(9-phenyl-9H-carbazol-3-yl)triphenylamine (abbreviation: PCBNBB), 9,9-dimethyl-N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]fluoren-2-amine (abbreviation: PCBAF), and N-phenyl-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9'-spirobi[9H-fluoren]-2-amine

(abbreviation: PCBASF); compounds having a carbazole skeleton, such as 1,3-bis(N-carbazolyl)benzene (abbreviation: mCP), 4,4'-di(N-carbazolyl)biphenyl (abbreviation: CBP), 3,6-bis(3,5-diphenylphenyl)-9-phenylcarbazole (abbreviation: CzTP), 3,3'-bis(9-phenyl-9H-carbazole) (abbreviation: PCCP), 3,9-bis(9-phenyl-9H-carbazol-3-yl)-9H-carbazole (abbreviation: PCCzPC), 9-(biphenyl-4-yl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: PCCzBP), 9,9'-bis(biphenyl-4-yl)-3,3'-bi-9H-carbazole (abbreviation: BisBPCz), 9,9'-bis(biphenyl-3-yl)-3,3'-bi-9H-carbazole (abbreviation: BismBPCz), 9-(biphenyl-3-yl)-9'-(biphenyl-4-yl)-9H,9'H-3,3'-bicarbazole (abbreviation: mBPCCBP), 9-(2-naphthyl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: β NCCP), 9-(3-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCmBP), 9-(4-biphenyl)-9'-(2-naphthyl)-3,3'-bi-9H-carbazole (abbreviation: PNCCBP), 9,9'-di-2-naphthyl-3,3'-9H,9'H-bicarbazole (abbreviation: BisPNCz), 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-3-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-5'-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':4',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, 9-(2-naphthyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-phenyl-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole (abbreviation: PCCzTp), 9,9'-bis(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(4-biphenyl)-9'-(triphenylen-2-yl)-3,3'-9H,9'H-bicarbazole, 9-(triphenylen-2-yl)-9'-[1,1':3',1''-terphenyl]-4-yl-3,3'-9H,9'H-bicarbazole, N,N-bis(9,9-dimethyl-9H-fluoren-2-yl)-9,9'-spirobi-9H-fluoren-1-amine, 9-[3-(triphenylsilyl)phenyl]-3,9'-bi-9H-carbazole (abbreviation: PSiCzCz), and 9'-[3-(triphenylsilyl)phenyl]-9'H-9,3':6',9''-tercarbazole (abbreviation: PSiCzGI); compounds having a thiophene skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzothiophene) (abbreviation: DBT3P-II), 2,8-diphenyl-4-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]dibenzothiophene (abbreviation: DBTFLP-III), and 4-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]-6-phenyldibenzothiophene (abbreviation: DBTFLP-IV); and compounds having a furan skeleton, such as 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzofuran) (abbreviation: DBF3P-II) and 4-{3-[3-(9-phenyl-9H-fluoren-9-yl)phenyl]phenyl}dibenzofuran (abbreviation: mmDBFFLBi-II).

Among the above compounds, the compound having an aromatic amine skeleton and the compound having a carbazole skeleton are preferable because these compounds are highly reliable and have a high hole-transport property to contribute to a reduction in driving voltage. In addition, the organic compounds given as examples of the material having a hole-transport property that can be used for the hole-transport layer can also be used.

[0268] The organic compound having an electron-transport property is preferably an organic compound having a π -electron deficient heteroaromatic ring. Examples of the organic compound having a π -electron deficient heteroaromatic ring include an organic compound that has a heteroaromatic ring having an azole skeleton, an organic compound that has a heteroaromatic ring having a pyridine skeleton, an organic compound that has a heteroaromatic ring having a diazine skeleton, and an organic compound that has a heteroaromatic ring having a triazine skeleton.

[0269] Among the above organic compounds, the organic compound that has a heteroaromatic ring having a diazine skeleton (a pyrimidine skeleton, a pyrazine skeleton, or a pyridazine skeleton), the organic compound that has a heteroaromatic ring having a pyridine skeleton, and the organic compound that has a heteroaromatic ring having a triazine skeleton are preferable because of their high reliability. In particular, the organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton and the organic compound that has a heteroaromatic ring having a triazine skeleton have a high electron-transport property to contribute to a reduction in driving voltage. A benzofuopyrimidine skeleton, a benzothienopyrimidine skeleton, a benzofuopyrazine skeleton, and a benzothienopyrazine skeleton are preferable because of their high acceptor properties and high reliability.

[0270] Preferable examples of the organic compound having a π -electron deficient heteroaromatic ring include the following organic compounds: organic compounds having an azole skeleton, such as 2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole (abbreviation: PBD), 3-(4-

biphenyl)-4-phenyl-5-(4-tert-butylphenyl)-1,2,4-triazole (abbreviation: TAZ), 1,3-bis[5-(p-tert-butylphenyl)-1,3,4-oxadiazol-2-yl]benzene (abbreviation: OXD-7), 9-[4-(5-phenyl-1,3,4-oxadiazol-2-yl)phenyl]-9H-carbazole (abbreviation: CO11), 2,2',2''-(1,3,5-benzenetriyl)tris(1-phenyl-1H-benzimidazole) (abbreviation: TPBI), 2-[3-(dibenzothiophen-4-yl)phenyl]-1-phenyl-1H-benzimidazole (abbreviation: mDBTBIm-II), and 4,4'-bis(5-methylbenzoxazol-2-yl)stilbene (abbreviation: BzOS); organic compounds that have a heteroaromatic ring having a pyridine skeleton, such as 3,5-bis[3-(9H-carbazol-9-yl)phenyl]pyridine (abbreviation: 35DCzPPy), 1,3,5-tri[3-(3-pyridyl)phenyl]benzene (abbreviation: TmPyPB), bathophenanthroline (abbreviation: BPhen), bathocuproine (abbreviation: BCP), 2,9-di(naphthalen-2-yl)-4,7-diphenyl-1,10-phenanthroline (abbreviation: NBPhen), 2,2'-(1,3-phenylene)bis(9-phenyl-1,10-phenanthroline) (abbreviation: mPPhen2P), 2-[3-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: mTpPPhen), 2-phenyl-9-(2-triphenylenyl)-1,10-phenanthroline (abbreviation: Ph-TpPhen), 2-[4-(9-phenanthrenyl)-1-naphthalenyl]-1,10-phenanthroline (abbreviation: PnNPhen), and 2-[4-(2-triphenylenyl)phenyl]-1,10-phenanthroline (abbreviation: pTpPPhen); organic compounds having a diazine skeleton, such as 2-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 2mDBTPDBq-II), 2-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mDBTBPDq-II), 2-[3'-(9H-carbazol-9-yl)biphenyl-3-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mCzBPDBq), 2-[4'-(9-phenyl-9H-carbazol-3-yl)-3,1'-biphenyl-1-yl]dibenzo[f,h]quinoxaline (abbreviation: 2mpPCBPDBq), 2-[4-(3,6-diphenyl-9H-carbazol-9-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 2CzPDBq-III), 7-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 7mDBTPDBq-II), 6-[3-(dibenzothiophen-4-yl)phenyl]dibenzo[f,h]quinoxaline (abbreviation: 6mDBTPDBq-II), 9-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]naphtho[1',2':4,5]furo[2,3-b]pyrazine (abbreviation: 9mDBtBPNfpr), 9-[3'-(dibenzothiophen-4-yl)biphenyl-4-yl]naphtho[1',2':4,5]furo[2,3-b]pyrazine (abbreviation: 9pmDBtBPNfpr), 4,6-bis[3-(phenanthren-9-yl)phenyl]pyrimidine (abbreviation: 4,6mPnP2Pm), 4,6-bis[3-(dibenzothiophen-4-yl)phenyl]pyrimidine (abbreviation: 4,6mDBTP2Pm-II), 4,6-bis[3-(9H-carbazol-9-yl)phenyl]pyrimidine (abbreviation: 4,6mCzP2Pm), 9,9'-[pyrimidine-4,6-diylbis(biphenyl-3,3'-diyl)]bis(9H-carbazole) (abbreviation: 4,6mCzBP2Pm), 8-(biphenyl-4-yl)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8BP-4mDBtPBfpm), 3,8-bis[3-(dibenzothiophen-4-yl)phenyl]benzofuro[2,3-b]pyrazine (abbreviation: 3,8mDBtP2Bfpr), 4,8-bis[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 4,8mDBtP2Bfpm), 8-[3'-(dibenzothiophen-4-yl)(biphenyl-3-yl)]naphtho[1',2':4,5]furo[3,2-d]pyrimidine (abbreviation: 8mDBtBPNfpm), 8-[(2,2'-binaphthalen)-6-yl]-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8(PN2)-4mDBtPBfpm), 2,2'-(pyridine-2,6-diyl)bis(4-phenylbenzo[h]quinazoline) (abbreviation: 2,6(P-Bqn)2Py), 2,2'-(pyridine-2,6-diyl)bis{4-[4-(2-naphthyl)phenyl]-6-phenylpyrimidine} (abbreviation: 2,6(NP-PPm)2Py), 6-(biphenyl-3-yl)-4-[3,5-bis(9H-carbazol-9-yl)phenyl]-2-phenylpyrimidine (abbreviation: 6mBP-4Cz2PPm), 2,6-bis(4-naphthalen-1-ylphenyl)-4-[4-(3-pyridyl)phenyl]pyrimidine (abbreviation: 2,4NP-6PyPPm), 4-[3,5-bis(9H-carbazol-9-yl)phenyl]-2-phenyl-6-(biphenyl-4-yl)pyrimidine (abbreviation: 6BP-4Cz2PPm), 7-[4-(9-phenyl-9H-carbazol-2-yl)quinazolin-2-yl]-7H-dibenzo[c,g]carbazole (abbreviation: PC-cgDBCzQz), 8-(p-terphenyl-3-yl)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm), and 2,2'-(2,2'-bipyridine-6,6'-diyl)bis(4-phenylbenzo[h]quinazoline) (abbreviation: 6,6'(P-Bqn)2BPy); and organic compounds that have a heteroaromatic ring having a triazine skeleton, such as 2-(biphenyl-4-yl)-4-phenyl-6-(9,9'-spirobi[9H-fluoren]-2-yl)-1,3,5-triazine (abbreviation: BP-SFTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-8-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn), 2-{3-[3-(benzo[b]naphtho[1,2-d]furan-6-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mBnfBPTzn-02), 2-{4-[3-(N-phenyl-9H-carbazol-3-yl)-9H-carbazol-9-yl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: PCCzPTzn), 9-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-9'-phenyl-

2,3'-bi-9H-carbazole (abbreviation: mPCCzPTzn-02), 2-[3'-(9,9-dimethyl-9H-fluorene-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mFBPTzn), 5-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-7,7-dimethyl-5H,7H-indeno[2,1-b]carbazole (abbreviation: mINc(II)PTzn), 2-{3-[3-(dibenzothiophen-4-yl)phenyl]phenyl}-4,6-diphenyl-1,3,5-triazine (abbreviation: mDBtBPTzn), 2,4,6-tris[3'-(pyridin-3-yl)biphenyl-3-yl]-1,3,5-triazine (abbreviation: TmPPPyTz), 2-[3-(2,6-dimethyl-3-pyridinyl)-5-(9-phenanthrenyl)phenyl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mPn-mDMePyPTzn), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-phenylindolo[2,3-a]carbazole (abbreviation: BP-Icz(II)Tzn), 2-[3'-(triphenyl-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mTpBPTzn), 3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]-9-phenyl-9H-carbazole (abbreviation: PCDBfTzn), 2-(biphenyl-3-yl)-4-phenyl-6-{8-[(1,1':4'',1''-terphenyl)-4-yl]-1-dibenzofuranyl}-1,3,5-triazine (abbreviation: mBP-TPDBfTzn), 2-[4-(2-naphthalenyl)phenyl]-4-phenyl-6-spiro[9H-fluorene-9,9'-(9H)xanthen]-4-yl-1,3,5-triazine (abbreviation: PNP-SFx(4)Tzn), 9,9'-{6-[3-(triphenylsilyl)phenyl]-1,3,5-triazine-2,4-diyl}bis(9H-carbazole) (abbreviation: SiTrzCz2), 2-phenyl-4,6-bis[3-(triphenylsilyl)phenyl]-1,3,5-triazine (abbreviation: mSiTrz), 11-[4-(biphenyl-4-yl)-6-phenyl-1,3,5-triazin-2-yl]-11,12-dihydro-12-(biphenyl-3-yl)indolo[2,3-a]carbazole (abbreviation: BP-mBPIcz(II)Tzn), 3-{3-[9-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzofuranyl]phenyl}-9-phenyl-9H-carbazole (abbreviation: mPCPDBfTzn), 9,9'-[6-(biphenyl-4-yl)-2-phenyl-1,3,5-triazine-4,3''-diyl]bis(9H-carbazole) (abbreviation: Cz-pmCzBPTzn), 3-phenyl-9-[4-phenyl-6-(9-phenyl-3-dibenzofuranyl)-1,3,5-triazin-2-yl]-9H-carbazole (abbreviation: PDBf-PCzTzn), 9-[4-(4,6-diphenyl-1,3,5-triazin-2-yl)-2-dibenzothiophenyl]-2-phenyl-9H-carbazole (abbreviation: PCzDBtTzn), and 2,4,6-tris(2-pyridyl)-1,3,5-triazine (abbreviation: 2Py3Tzn). The organic compound that has a heteroaromatic ring having a diazine skeleton, the organic compound that has a heteroaromatic ring having a pyridine skeleton, and the organic compound that has a heteroaromatic ring having a triazine skeleton are preferable because of their high reliability. In particular, the organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton and the organic compound that has a heteroaromatic ring having a triazine skeleton have a high electron-transport property to contribute to a reduction in driving voltage.

[0271] As the TADF material that can be used as the host material, the above materials mentioned as the TADF material that can be used as the emission center substance can also be used. When the TADF material is used as the host material, triplet excitation energy generated in the TADF material is converted into singlet excitation energy by reverse intersystem crossing and transferred to the light-emitting substance, whereby the emission efficiency of the light-emitting device can be increased. Here, the TADF material functions as an energy donor, and the light-emitting substance functions as an energy acceptor.

[0272] This is very effective in the case where the light-emitting substance is a fluorescent substance. In that case, the Si level of the TADF material is preferably higher than that of the fluorescent substance in order that high emission efficiency can be achieved. Furthermore, the T.sub.1 level of the TADF material is preferably higher than the Si level of the fluorescent substance. Therefore, the T.sub.1 level of the TADF material is preferably higher than that of the fluorescent substance.

[0273] It is also preferable to use a TADF material that emits light whose wavelength overlaps with the wavelength of the lowest-energy absorption band of the fluorescent substance. This enables smooth transfer of excitation energy from the TADF material to the fluorescent substance and accordingly enables efficient light emission, which is preferable.

[0274] In order to efficiently generate singlet excitation energy from the triplet excitation energy by reverse intersystem crossing, carrier recombination preferably occurs in the TADF material. It is also preferable that the triplet excitation energy generated in the TADF material not be transferred to the triplet excitation energy of the fluorescent substance. For that reason, the fluorescent substance preferably has a protective group around a luminophore (a skeleton that brings about

light emission) of the fluorescent substance. As the protective group, a substituent having no π bond and a saturated hydrocarbon are preferably used. Specific examples include an alkyl group having 3 to 10 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 10 carbon atoms, and a trialkylsilyl group having 3 to 10 carbon atoms. It is further preferable that the fluorescent substance have a plurality of protective groups. The substituents having no π bond are poor in carrier transport performance, whereby the TADF material and the luminophore of the fluorescent substance can be made away from each other with little influence on carrier transportation or carrier recombination. Here, the luminophore refers to an atomic group (skeleton) that brings about light emission in a fluorescent substance. The luminophore is preferably a skeleton having a π bond, further preferably has an aromatic ring, and still further preferably has a condensed aromatic ring or a condensed heteroaromatic ring. Examples of the luminophore include a phenanthrene skeleton, a stilbene skeleton, an acridone skeleton, a phenoxazine skeleton, a phenothiazine skeleton, a naphthalene skeleton, an anthracene skeleton, a fluorene skeleton, a chrysene skeleton, a triphenylene skeleton, a tetracene skeleton, a pyrene skeleton, a perylene skeleton, a coumarin skeleton, a quinacridone skeleton, and a naphthobisbenzofuran skeleton. Specifically, a fluorescent substance having any of a naphthalene skeleton, an anthracene skeleton, a fluorene skeleton, a chrysene skeleton, a triphenylene skeleton, a tetracene skeleton, a pyrene skeleton, a perylene skeleton, a coumarin skeleton, a quinacridone skeleton, and a naphthobisbenzofuran skeleton is preferable because of its high fluorescence quantum yield.

[0275] In the case where a fluorescent substance is used as the emission center substance, a material having an anthracene skeleton is suitably used as the host material. The use of a substance having an anthracene skeleton as the host material for the fluorescent substance makes it possible to obtain a light-emitting layer with high emission efficiency and high durability. Among the substances having an anthracene skeleton, a substance having a diphenylanthracene skeleton, in particular, a substance having a 9,10-diphenylanthracene skeleton, is chemically stable and thus is preferably used as the host material. The host material preferably has a carbazole skeleton to have higher hole-injection and hole-transport properties; further preferably, the host material has a benzocarbazole skeleton in which a benzene ring is further condensed to a carbazole skeleton, because the HOMO level of the host material having a benzocarbazole skeleton is higher than that of the host material having a carbazole skeleton by approximately 0.1 eV and the host material having a benzocarbazole skeleton is thus easier for holes to enter than the host material having a carbazole skeleton. In particular, the host material preferably has a dibenzocarbazole skeleton, because the HOMO level of the host material having a dibenzocarbazole skeleton is higher than that of the host material having a carbazole skeleton by approximately 0.1 eV, the host material having a dibenzocarbazole skeleton is thus easier for holes to enter than the host material having a carbazole skeleton, and the host material having a dibenzocarbazole skeleton has a higher hole-transport property and higher heat resistance than the host material having a carbazole skeleton. Accordingly, a substance that has both a 9,10-diphenylanthracene skeleton and a carbazole skeleton (or a benzocarbazole or dibenzocarbazole skeleton) is further preferable as the host material. Note that in terms of the hole-injection and hole-transport properties described above, instead of a carbazole skeleton, a benzofluorene skeleton or a dibenzofluorene skeleton may be used. Examples of such a substance include 9-phenyl-3-[4-(10-phenyl-9-anthryl)phenyl]-9H-carbazole (abbreviation: PCzPA), 3-[4-(1-naphthyl)phenyl]-9-phenyl-9H-carbazole (abbreviation: PCPN), 9-[4-(10-phenyl-9-anthracenyl)phenyl]-9H-carbazole (abbreviation: CzPA), 7-[4-(10-phenyl-9-anthryl)phenyl]-7H-dibenzo[c,g]carbazole (abbreviation: cgDBCzPA), 6-[3-(9,10-diphenyl-2-anthryl)phenyl]benzo[b]naphtho[1,2-d]furan (abbreviation: 2mBnfPPA), 9-phenyl-10-[4-(9-phenyl-9H-fluoren-9-yl)biphenyl-4'-yl]anthracene (abbreviation: FLPPA), 9-(1-naphthyl)-10-[4-(2-naphthyl)phenyl]anthracene (abbreviation: α N-QNPAnth), 9-(1-naphthyl)-10-(2-naphthyl)anthracene (abbreviation: α,β ADN), 2-(10-phenylanthracen-9-yl)dibenzofuran, 2-(10-phenyl-9-anthracenyl)benzo[b]naphtho[2,3-d]furan (abbreviation: Bnf(II)PhA), 9-(2-naphthyl)-10-

[3-(2-naphthyl)phenyl]anthracene (abbreviation: PN-mQNPAnth), and 1-{4-[10-(biphenyl-4-yl)-9-anthracenyl]phenyl}-2-ethyl-1H-benzimidazole (abbreviation: EtBImPBPhA). In particular, CzPA, cgDBCzPA, 2mBnfPPA, and PCzPA exhibit excellent properties and thus are preferably selected. [0276] Note that the host material may be a mixture of a plurality of kinds of substances; in the case of using a mixed host material, it is preferable to mix a material having an electron-transport property with a material having a hole-transport property. By mixing the material having an electron-transport property with the material having a hole-transport property, the transport property of the light-emitting layer **113** can be easily adjusted and a recombination region can be easily controlled. The weight ratio of the content of the material having a hole-transport property to the content of the material having an electron-transport property may be 1:19 to 19:1.

[0277] Note that a phosphorescent substance can be used as part of the mixed material. When a fluorescent substance is used as a light-emitting substance, a phosphorescent substance can be used as an energy donor for supplying excitation energy to the fluorescent substance.

[0278] These mixed materials may form an exciplex. These mixed materials are preferably selected so as to form an exciplex that exhibits light emission whose wavelength overlaps with the wavelength of the lowest-energy absorption band of the light-emitting substance, in which case energy can be transferred smoothly and light emission can be obtained efficiently. The use of such a structure is preferable because the driving voltage can also be reduced.

[0279] The first electron-transport layer **114_1** is a layer including a substance that has an electron-transport property. The substance having an electron-transport property preferably has an electron mobility higher than or equal to 1×10^{-7} cm²/Vs, further preferably higher than or equal to 1×10^{-6} cm²/Vs when the square root of the electric field strength [V/cm] is 600. Note that any other substance can also be used as long as the substance has a property of transporting more electrons than holes. The above substance is preferably an organic compound that has a π -electron deficient heteroaromatic ring. The organic compound that has a π -electron deficient heteroaromatic ring is preferably one or more of an organic compound that has a heteroaromatic ring having an azole skeleton, an organic compound that has a heteroaromatic ring having a pyridine skeleton, an organic compound that has a heteroaromatic ring having a diazine skeleton, and an organic compound that has a heteroaromatic ring having a triazine skeleton, and is particularly preferably an organic compound that has a heteroaromatic ring having a triazine skeleton.

[0280] As the organic compound having an electron-transport property that can be used in the first electron-transport layer **114_1**, any of the aforementioned organic compounds that can be used as the organic compound having an electron-transport property that serves as the host material in the first light-emitting layer **113_1** and the second light-emitting layer **113_2** can be used. Among the above organic compounds, the organic compound that has a heteroaromatic ring having a diazine skeleton, the organic compound that has a heteroaromatic ring having a pyridine skeleton, and the organic compound that has a heteroaromatic ring having a triazine skeleton are preferable because of having high reliability. In particular, the organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton and the organic compound that has a heteroaromatic ring having a triazine skeleton have a high electron-transport property to contribute to a reduction in driving voltage.

[0281] The second electron-transport layer **114_2** is, as described above, a layer including the first organic compound having a triazine skeleton. Since the details have already been described, the description is omitted here.

[0282] Note that the first electron-transport layer **114_1** preferably includes the organic compound having a triazine skeleton to reduce power consumption. In particular, the first electron-transport layer **114_1** preferably includes the same organic compound having a triazine skeleton as the first organic compound having a triazine skeleton that is included in the second electron-transport layer **1142**, which inhibits the complication of a manufacturing apparatus and is advantageous also in

terms of raw material procurement cost.

[0283] Alternatively, in the case where the first electron-transport layer **114_1** includes an organic compound not having a triazine skeleton, the light-emitting device can have favorable characteristics owing to easy control of carrier transport. The organic compound not having a triazine skeleton is preferably an organic compound that has a heteroaromatic ring having a pyridine skeleton or an organic compound that has a heteroaromatic ring having a diazine (pyrimidine or pyrazine) skeleton.

[0284] The intermediate layer **116** includes the second organic compound having a phenanthroline skeleton. As illustrated in FIG. **1A**, the intermediate layer **116** preferably includes a first layer **119** including the second organic compound having a phenanthroline skeleton. The intermediate layer **116** preferably includes the second layer **117** including the ninth organic compound having a hole-transport property and the substance having an acceptor property. The second layer **117** is positioned closer to the second electrode **102** than the first layer **119** is. The intermediate layer **116** may include a third layer **118** between the first layer **119** and the second layer **117**.

[0285] The details of the first layer are described above and not repeated here.

[0286] The first layer **119** may further include an organic compound having an electron-transport property. As the organic compound having an electron-transport property, any of the aforementioned organic compounds that can be used as the organic compound having an electron-transport property that serves as the host material in the first light-emitting layer **113_1** and the second light-emitting layer **113_2** can also be used. The organic compound having an electron-transport property is preferably an organic compound having two or more heteroaromatic rings that are bonded or condensed to each other and that have three or more heteroatoms in total, in which case the resistance to a photolithography method can be improved and an increase in driving voltage can be inhibited.

[0287] Note that the first layer **119** may have a stacked-layer structure of a layer including an organic compound and a layer including a metal or a metal compound and positioned closer to the cathode than the layer including an organic compound is, or may be a mixed layer of an organic compound and a metal or a metal compound. The first layer **119** is preferably the mixed layer because it requires a smaller number of film formation chambers and a lower manufacturing cost and contributes to an improvement in the stability of the light-emitting device.

[0288] In the case where the organic compound and the metal or the metal compound are mixed, the organic compound and the metal or the metal compound tend to show substantially the same distribution when the first layer **119** is analyzed in the thickness direction. That is, when the organic compound is uniformly distributed, the metal or the metal compound is also substantially uniformly distributed. In the case of the stacked-layer structure of the layer including the organic compound and the layer including the metal or the metal compound, the metal or the metal compound is sometimes diffused from the layer including the metal or the metal compound and detected also in a region other than the layer but shows a distribution different from that of the organic compound; thus, the analysis results of diffusion and mixing can be distinguished from each other.

[0289] The second layer **117** preferably includes the ninth organic compound having a hole-transport property. The second layer **117** preferably further includes a substance exhibiting an acceptor property, and the substance exhibiting an acceptor property is preferably an organic compound exhibiting an acceptor property with respect to the ninth organic compound.

[0290] In the case where the second layer **117** includes the ninth organic compound and the substance exhibiting an acceptor property with respect to the ninth organic compound, holes are generated by charge separation, and the holes are injected into the second light-emitting unit **502** on the cathode side through the ninth organic compound when voltage is applied between the first electrode **101** and the second electrode **102**. Thus, the light-emitting device **130** of one embodiment of the present invention can have a low driving voltage.

[0291] As the ninth organic compound having a hole-transport property, any of a variety of organic compounds such as aromatic amine compounds, heteroaromatic compounds, aromatic hydrocarbons, and high molecular compounds (e.g., oligomers, dendrimers, and polymers) can be used. Note that the ninth organic compound preferably has a hole mobility higher than or equal to 1×10^{-6} cm²/Vs. The ninth organic compound preferably has a condensed aromatic hydrocarbon ring or a π -electron rich heteroaromatic ring. As the condensed aromatic hydrocarbon ring, an anthracene ring, a naphthalene ring, or the like is preferable. As the π -electron rich heteroaromatic ring, a condensed aromatic ring having at least one of a pyrrole skeleton, a furan skeleton, and a thiophene skeleton is preferable; specifically, a carbazole ring, a dibenzothiophene ring, or a ring in which an aromatic ring or a heteroaromatic ring is further condensed to a carbazole ring or a dibenzothiophene ring is preferable.

[0292] Such an organic compound having a hole-transport property further preferably has any of a carbazole skeleton, a dibenzofuran skeleton, a dibenzothiophene skeleton, and an anthracene skeleton. In particular, an aromatic amine having a substituent that has a dibenzofuran ring or a dibenzothiophene ring, an aromatic monoamine that has a naphthalene ring, or an aromatic monoamine in which a 9-fluorenyl group is bonded to nitrogen of an amine through an arylene group may be used. Note that the organic compound having a hole-transport property preferably has an N,N-bis(4-biphenyl)amino group to enable fabricating a light-emitting device having a long lifetime.

[0293] The above-described organic compound having a hole-transport property can specifically be any of the organic compounds given as examples of the organic compound having a hole-transport property that can be used in the hole-injection layer **111**.

[0294] The substance having an acceptor property can be, for example, any of the substances given as examples of the organic compound having an acceptor property that can be used in the hole-injection layer **111**. An organic compound having at least one of a halogen group and a cyano group is particularly preferable, and an organic compound having at least one of fluorine and a cyano group is further preferable. Note that it is further preferable that the total number of halogen groups (fluorines) and cyano groups of the organic compound be four or more. Examples of the organic compound having at least one of a halogen group and a cyano group include $\alpha, \alpha', \alpha''$ -1,2,3-cyclopropanetriylidenetris[4-cyano-2,3,5,6-tetrafluorobenzeneacetonitrile], $\alpha, \alpha', \alpha''$ -1,2,3-cyclopropanetriylidenetris[2,6-dichloro-3,5-difluoro-4-(trifluoromethyl)benzeneacetonitrile], and $\alpha, \alpha', \alpha''$ -1,2,3-cyclopropanetriylidenetris[2,3,4,5,6-pentafluorobenzeneacetonitrile].

[0295] Note that the substance having an acceptor property preferably has an electron-accepting property with respect to the ninth organic compound having a hole-transport property. When the substance having an acceptor property has an electron-accepting property with respect to the ninth organic compound, charge separation occurs and the second layer **117** can function as a charge-generation layer and functions as an intermediate layer of the tandem light-emitting device. A signal is preferably observed by electron spin resonance in the second layer **117**. For example, the density of spins attributed to a signal observed at a g-factor of approximately 2.00 is preferably higher than or equal to 1×10^{17} spins/cm³, further preferably higher than or equal to 1×10^{18} spins/cm³, still further preferably higher than or equal to 1×10^{19} spins/cm³.

[0296] The third layer **118** includes a substance having an electron-transport property and has functions of preventing the interaction between the first layer **119** and the second layer **117** and smoothly transferring and receiving electrons therebetween to reduce the driving voltage, and reducing the interaction between the first layer **119** and the second layer **117** to improve the reliability, for example.

[0297] The LUMO level of the substance having an electron-transport property that is included in the third layer **118** is preferably between the LUMO level of the substance having an acceptor property in the second layer **117** and the LUMO level of the organic compound included in a layer

(e.g., the first electron-transport layer **114_1** in the first light-emitting unit **501** in FIG. 1A) which is in contact with the first layer **119** in the light-emitting unit on the anode side.

[0298] A specific energy level of the LUMO level of the substance having an electron-transport property that is used in the third layer **118** is preferably higher than or equal to -5.0 eV, further preferably higher than or equal to -5.0 eV and lower than or equal to -3.0 eV, still further preferably higher than or equal to -4.30 eV and lower than or equal to -3.00 eV, yet further preferably higher than or equal to -4.30 eV and lower than or equal to -3.30 eV, in which case an increase in driving voltage can be inhibited. Note that the substance having an electron-transport property that is used in the third layer **118** is preferably a phthalocyanine-based material or a metal complex having a metal-oxygen bond and an aromatic ligand.

[0299] Specific examples of the substance having an electron-transport property that is used in the third layer **118** include perylenetetracarboxylic acid derivatives such as diquinoxalino[2,3-a:2',3'-c]phenazine (abbreviation: HATNA), 2,3,8,9,14,15-hexafluorodiquinoxalino[2,3-a:2',3'-c]phenazine (abbreviation: HATNA-F6), 3,4,9,10-perylenetetracarboxylic diimide (abbreviation: PTCDI), and 3,4,9,10-perylenetetracarboxyl-bis-benzimidazole (abbreviation: PTCBI), (C.sub.60-I.sub.h)[5,6]fullerene (abbreviation: C.sub.60), and (C.sub.70-D.sub.5h)[5,6]fullerene (abbreviation: C.sub.70). It is also possible to use a compound having a heterophane skeleton, which is a cyclophane skeleton having a hetero ring; for example, a phthalocyanine compound such as phthalocyanine (abbreviation: H.sub.2Pc) can be used as the compound. Alternatively, it is possible to use a metal phthalocyanine containing copper, zinc, cobalt, iron, chromium, nickel, or the like or a derivative thereof, such as copper phthalocyanine (abbreviation: CuPc), zinc phthalocyanine (abbreviation: ZnPc), cobalt phthalocyanine (abbreviation: CoPc), iron phthalocyanine (abbreviation: FePc), tin phthalocyanine (abbreviation: SnPc), tin oxide phthalocyanine (abbreviation: SnOPc), titanium oxide phthalocyanine (abbreviation: TiOPc), or vanadium oxide phthalocyanine (abbreviation: VOPc). It is particularly preferable to use a phthalocyanine-based metal complex such as copper phthalocyanine or zinc phthalocyanine or 2,3,8,9,14,15-hexafluorodiquinoxalino[2,3-a:2',3'-c]phenazine.

[0300] The thickness of the third layer **118** is preferably greater than or equal to 1 nm and less than or equal to 10 nm, further preferably greater than or equal to 2 nm and less than or equal to 5 nm.

[0301] Note that the second light-emitting unit **502** includes no hole-injection layer because the second layer **117** in the intermediate layer **116** functions as a hole-injection layer; however, the second light-emitting unit **502** may include a hole-injection layer.

[0302] The second electrode **102** includes the cathode. The second electrode **102** may have a stacked-layer structure, in which case a layer in contact with the organic compound layer **103** functions as the cathode. The cathode is preferably formed using a metal, an alloy, an electrically conductive compound, or a mixture thereof each having a low work function (specifically, lower than or equal to 3.8 eV), for example. Specific examples of such a cathode material include elements belonging to Group 1 and Group 2 of the periodic table, such as alkali metals (e.g., lithium (Li) or cesium (Cs)), magnesium (Mg), calcium (Ca), and strontium (Sr), alloys containing any of these elements (e.g., MgAg and AlLi), rare earth metals such as europium (Eu) and ytterbium (Yb), and alloys containing any of these rare earth metals. Specific examples thereof include alkali metals, alkaline earth metals, rare earth metals, compounds thereof, and complexes thereof, such as lithium fluoride (LiF), cesium fluoride (CsF), calcium fluoride (CaF.sub.2), 8-hydroxyquinolinato-lithium (abbreviation: Liq), and ytterbium (Yb), and electrides. Examples of an electride include substances in which electrons are added at high concentration to calcium oxide-aluminum oxide. Note that a mixture of two or more of these materials may be used as a cathode material. In the case where the second electrode **102** has a stacked-layer structure, a material having high conductivity can be used for the layer(s) other than the cathode, regardless of the work function.

[0303] Note that the second electron-transport layer **114_2** is preferably in contact with the second

electrode **102**. When the second electron-transport layer **114_2** is in contact with the second electrode **102**, the light-emitting device can have excellent electron-injection and electron-transport properties, a low driving voltage, and low power consumption.

[0304] When the second electrode **102** is formed using a material that transmits visible light, the light-emitting device can emit light from the second electrode **102** side.

[0305] Films of these conductive materials can be formed by a dry process such as a vacuum evaporation method or a sputtering method, an ink-jet method, a spin coating method, or the like. Alternatively, a wet process using a sol-gel method or a wet process using a paste of a metal material may be employed.

[0306] The organic compound layer **103** can be formed by any of a variety of methods, including a dry process and a wet process. For example, a vacuum evaporation method, a gravure printing method, an offset printing method, a screen printing method, an ink-jet method, a spin coating method, or the like may be used.

[0307] Different film formation methods may be used to form the electrodes or the layers described above.

[0308] FIG. **1C** illustrates two adjacent light-emitting devices (a light-emitting device **130a** and a light-emitting device **130b**) included in a display device of one embodiment of the present invention.

[0309] The light-emitting device **130a** includes an organic compound layer **103a** between a first electrode **101a** and the second electrode **102** over an insulating layer **175**. The organic compound layer **103a** has a structure in which a first light-emitting unit **501a** and a second light-emitting unit **502a** are stacked with an intermediate layer **116a** therebetween. Although FIG. **1C** illustrates an example in which the two light-emitting units are stacked, three or more light-emitting units may be stacked. The first light-emitting unit **501a** includes a hole-injection layer **111a**, a first hole-transport layer **112a_1**, a first light-emitting layer **113a_1**, and a first electron-transport layer **114a_1**. The intermediate layer **116a** includes a second layer **117a**, a third layer **118a**, and a first layer **119a**. The third layer **118a** may be present or absent. The second light-emitting unit **502a** includes a second hole-transport layer **112a_2**, a second light-emitting layer **113a_2**, and a second electron-transport layer **114a_2**.

[0310] The light-emitting device **130b** includes an organic compound layer **103b** between a first electrode **101b** and the second electrode **102** over the insulating layer **175**. The organic compound layer **103b** has a structure in which a first light-emitting unit **501b** and a second light-emitting unit **502b** are stacked with an intermediate layer **116b** therebetween. Although FIG. **1C** illustrates an example in which the two light-emitting units are stacked, three or more light-emitting units may be stacked. The first light-emitting unit **501b** includes a hole-injection layer **111b**, a first hole-transport layer **112b_1**, a first light-emitting layer **113b_1**, and a first electron-transport layer **114b_1**. The intermediate layer **116b** includes a second layer **117b**, a third layer **118b**, and a first layer **119b**. The third layer **118b** may be present or absent. The second light-emitting unit **502b** includes a second hole-transport layer **112b_2**, a second light-emitting layer **113b_2**, and a second electron-transport layer **114b_2**.

[0311] The second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** preferably include the first organic compound having a triazine skeleton. The first layer **119a** and the first layer **119b** each include the second organic compound having a phenanthroline skeleton.

[0312] The first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** preferably emit light of similar colors. The emission center substance included in the first light-emitting layer **113a_1** and the emission center substance included in the second light-emitting layer **113a_2** are preferably compounds whose emission spectra have a difference in maximum peak wavelength less than or equal to 30 nm, further preferably less than or equal to 20 nm, still further preferably less than or equal to 10 nm. It is further preferable that the first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** include the same emission center substance. Furthermore, the

first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** are preferably made of the same material. It is preferable that one of the first light-emitting layer **113a_1** and the second light-emitting layer **113a_2**, further preferably both of them, have the above-described structure of the light-emitting layer of one embodiment of the present invention.

[0313] The first light-emitting layer **113b_1** and the second light-emitting layer **113b_2** preferably emit light of similar colors. The emission center substance included in the first light-emitting layer **113b_1** and the emission center substance included in the second light-emitting layer **113b_2** are preferably compounds whose emission spectra have a difference in maximum peak wavelength less than or equal to 30 nm, further preferably less than or equal to 20 nm, still further preferably less than or equal to 10 nm. It is further preferable that the first light-emitting layer **113b_1** and the second light-emitting layer **113b_2** include the same emission center substance. Furthermore, the first light-emitting layer **113b_1** and the second light-emitting layer **113b_2** are preferably made of the same material. It is preferable that one of the first light-emitting layer **113b_1** and the second light-emitting layer **113b_2**, further preferably both of them, have the above-described structure of the light-emitting layer of one embodiment of the present invention.

[0314] It is preferable that the first light-emitting layer **113a_1** and the first light-emitting layer **113b_1** be separated from each other and the second light-emitting layer **113a_2** and the second light-emitting layer **113b_2** be separated from each other. It is preferable that the emission color(s) of the first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** be different from the emission color(s) of the first light-emitting layer **113b_1** and the second light-emitting layer **113b_2**. It is preferable that the emission center substance included in the first light-emitting layer **113a_1** and the emission center substance included in the first light-emitting layer **113b_1** be different from each other and the emission center substance included in the second light-emitting layer **113a_2** and the emission center substance included in the second light-emitting layer **113b_2** be different from each other.

[0315] Note that each of the pairs of the hole-injection layers **111a** and **111b**, the first hole-transport layers **112a_1** and **112b_1**, the first electron-transport layers **114a_1** and **114b_1**, the intermediate layers **116a** and **116b** (the second layers **117a** and **117b**, the third layers **118a** and **118b**, and the first layers **119a** and **119b**), the second hole-transport layers **112a_2** and **112b_2**, and the second electron-transport layers **114a_2** and **114b_2** may be one continuous layer or may be separate layers independent of each other between the light-emitting device **130a** and the light-emitting device **130b**. When these layers are continuous layers, the light-emitting devices can be fabricated with high productivity at low cost. When the layers are separate layers between the light-emitting devices, the layers can be formed using materials suitable for their emission colors, thereby enabling the light-emitting devices or a display device to have favorable characteristics. In particular, the second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** are preferably one continuous layer, in which case both the light-emitting device **130a** and the light-emitting device **130b** can have favorable characteristics.

[0316] The second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** being one continuous layer means that the second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** are made of the same material. That is, when the second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** are made of the same material, both the light-emitting device **130a** and the light-emitting device **130b** can have favorable characteristics. It is further preferable that the second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** have similar structures, and it is still further preferable that the second electron-transport layer **114a_2** and the second electron-transport layer **114b_2** have the same structure.

[0317] Furthermore, in the case where the emission center substances included in the first light-emitting layers **113a_1** and **113b_1** are different from each other and the emission center substances included in the second light-emitting layers **113a_2** and **113b_2** are different from each

other (e.g., in the case where the first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** are blue fluorescent layers and the first light-emitting layer **113b_1** and the second light-emitting layer **113b_2** are green phosphorescent layers, in the case where the first light-emitting layers **113a_1** and **113a_2** are blue fluorescent layers and the first light-emitting layers **113b_1** and **113b_2** are red phosphorescent layers, or in the case where the first light-emitting layers **113a_1** and **113a_2** are green phosphorescent layers and the first light-emitting layers **113b_1** and **113b_2** are red phosphorescent layers), the light-emitting layers of the light-emitting devices **130a** and **130b** have different carrier balances. Therefore, in order to improve the performance of each of the light-emitting devices **130a** and **130b**, it is usually necessary to select and use an appropriate intermediate layer and an appropriate electron-transport layer for each light-emitting device. However, even when the second electron-transport layers **114a_2** and **114b_2** have the same structure, the use of the first organic compound having a triazine skeleton in the second electron-transport layers **114a_2** and **114b_2** and the use of the second organic compound having a phenanthroline skeleton in the first layers **119a** and **119b** can improve the performance of each of the light-emitting devices **130a** and **130b**. That is, both the productivity and the performance can be improved. Note that the first layers **119a** and **119b** may have the same structure.

[0318] Note that one continuous layer is so-called common layer formed across the light-emitting devices **130a** and **130b**.

[0319] FIG. 2A is a modification example of FIG. 1C. The light-emitting device **130a** and a light-emitting device **130b1** emit light of different colors and thus have different optical path lengths between the electrodes for amplification of emitted light using microcavity. In the light-emitting device **130b1**, the distance between the electrodes can be adjusted by thickening light-emitting layers such as a light-emitting layer **113b_11** and a light-emitting layer **113b_21**. Alternatively, the optical path length may be changed by thickening or adding a functional layer such as a hole-transport layer **112b_21**.

[0320] FIG. 2B illustrates three adjacent light-emitting devices (the light-emitting device **130a**, the light-emitting device **130b1**, and a light-emitting device **130c**) included in a display device of one embodiment of the present invention.

[0321] The light-emitting device **130c** includes an organic compound layer **103c** between a first electrode **101c** and the second electrode **102** over the insulating layer **175**. The organic compound layer **103c** has a structure where a first light-emitting unit **501c** and a second light-emitting unit **502c** are stacked with an intermediate layer **116c** therebetween. Although FIG. 2B illustrates an example in which the two light-emitting units are stacked, three or more light-emitting units may be stacked. The first light-emitting unit **501c** includes a hole-injection layer **111c**, a first hole-transport layer **112c_1**, a first light-emitting layer **113c_1**, and a first electron-transport layer **114c_1**. The intermediate layer **116c** includes a second layer **117c**, a third layer **118c**, and a first layer **119c**. The third layer **118c** may be present or absent. The second light-emitting unit **502c** includes a second hole-transport layer **112c_2**, a second light-emitting layer **113c_2**, and a second electron-transport layer **114c_2**.

[0322] It is assumed here that the light-emitting device **130c** emits light whose wavelength is shorter than those of light from the light-emitting devices **130a** and **130b1**. The distance between the electrodes in the light-emitting device **130c** is adjusted by the thicknesses of the first light-emitting layer **113c_1** and the second light-emitting layer **113c_2**, which are smaller than those of the light-emitting layers in the other two light-emitting devices.

[0323] The second electron-transport layer **114c_2** includes the first organic compound having a triazine skeleton. The first layer **119c** includes the second organic compound having a phenanthroline skeleton.

[0324] The first light-emitting layer **113c_1** and the second light-emitting layer **113c_2** preferably emit light of similar colors. The emission center substance included in the first light-emitting layer **113c_1** and the emission center substance included in the second light-emitting layer **113c_2** are

preferably compounds whose emission spectra have a difference in maximum peak wavelength less than or equal to 30 nm, further preferably less than or equal to 20 nm, still further preferably less than or equal to 10 nm. It is further preferable that the first light-emitting layer **113c_1** and the second light-emitting layer **113c_2** include the same emission center substance. Furthermore, the first light-emitting layer **113c_1** and the second light-emitting layer **113c2** are preferably made of the same material. It is preferable that one of the first light-emitting layer **113c_1** and the second light-emitting layer **113c_2**, further preferably both of them, have the above-described structure of the light-emitting layer of one embodiment of the present invention.

[0325] It is preferable that the first light-emitting layer **113a_1** and the first light-emitting layer **113c_1** be separated from each other and the second light-emitting layer **113a_2** and the second light-emitting layer **113c_2** be separated from each other. It is preferable that the emission color(s) of the first light-emitting layer **113a_1** and the second light-emitting layer **113a_2** be different from the emission color(s) of the first light-emitting layer **113c_1** and the second light-emitting layer **113c_2**. It is preferable that the emission center substance included in the first light-emitting layer **113a_1** and the emission center substance included in the first light-emitting layer **113c_1** be different from each other and the emission center substance included in the second light-emitting layer **113a_2** and the emission center substance included in the second light-emitting layer **113c_2** be different from each other.

[0326] Note that each of the pairs of the hole-injection layers **111a** and **111c**, the first hole-transport layers **112a_1** and **112c_1**, the first electron-transport layers **114a_1** and **114c_1**, the intermediate layers **116a** and **116c** (the second layers **117a** and **117c**, the third layers **118a** and **118c**, and the first layers **119a** and **119c**), and the second hole-transport layers **112a_2** and **112c_2** in this example are separate layers independent of each other between the light-emitting device **130a** and the light-emitting device **130c**, and the second electron-transport layers **114a_2** and **114c_2** in this example are a continuous layer. In this manner, one light-emitting device may include both continuous and separate layers. This allows the light-emitting device or the display device to balance productivity and characteristics. In particular, the second electron-transport layer **114a_2** and the second electron-transport layer **114c_2** are preferably one continuous layer, in which case both the light-emitting device **130a** and the light-emitting device **130c** can have favorable characteristics.

[0327] In the case where light-emitting devices exhibiting three colors consist of, for example, two light-emitting devices including fluorescent emission center substances and one light-emitting device including a phosphorescent emission center substance, the light-emitting devices including the fluorescent emission center substances preferably have one continuous carrier-transport layer, and the light-emitting device including the phosphorescent emission center substance preferably has a carrier-transport layer separated from that in the light-emitting devices exhibiting the other emission colors. Alternatively, in the case where light-emitting devices exhibiting three colors consist of two light-emitting devices including phosphorescent emission center substances and one light-emitting device including a fluorescent emission center substance, the light-emitting devices including the phosphorescent emission center substances preferably have one continuous carrier-transport layer, and the light-emitting device including the fluorescent emission center substance preferably has a carrier-transport layer separated from that in the light-emitting devices exhibiting the other emission colors.

[0328] The light-emitting device of one embodiment of the present invention that has such a structure can have high current efficiency, low energy loss, and favorable characteristics. The display device of one embodiment of the present invention that includes such a light-emitting device can achieve low power consumption, high reliability, high-luminance display, and high visibility. This embodiment can be freely combined with any of the other embodiments.

Embodiment 2

[0329] In this embodiment, a display device manufactured using the light-emitting device described in Embodiment 1 is described with reference to FIGS. **3A** and **3B**. Note that FIG. **3A** is a

top view of the display device and FIG. 3B is a cross-sectional view taken along the lines A-B and C-D in FIG. 3A. This display device includes a driver circuit portion (source line driver circuit) **601**, a pixel portion **602**, and a driver circuit portion (gate line driver circuit) **603**, which are to control light emission of the light-emitting device and illustrated with dotted lines. Reference numeral **604** denotes a sealing substrate; **605**, a sealing material; and **607**, a space surrounded by the sealing material **605**.

[0330] Reference numeral **608** denotes a wiring for transmitting signals to be input to the source line driver circuit **601** and the gate line driver circuit **603** and receiving signals such as a video signal, a clock signal, a start signal, and a reset signal from a flexible printed circuit (FPC) **609** serving as an external input terminal. Although only the FPC is illustrated here, a printed wiring board (PWB) may be attached to the FPC. The display device in this specification includes, in its category, not only the display device itself but also the display device provided with the FPC or the PWB.

[0331] Next, a cross-sectional structure is described with reference to FIG. 3B. The driver circuit portions and the pixel portion are formed over an element substrate **610**; FIG. 3B illustrates the source line driver circuit **601**, which is a driver circuit portion, and one pixel in the pixel portion **602**.

[0332] The element substrate **610** may be a substrate formed of glass, quartz, an organic resin, a metal, an alloy, or a semiconductor or a plastic substrate formed of fiber reinforced plastic (FRP), polyvinyl fluoride (PVF), polyester, or an acrylic resin.

[0333] The structure of transistors used in the pixels and the driver circuits is not particularly limited. For example, inverted staggered transistors may be used, or staggered transistors may be used. Furthermore, top-gate transistors or bottom-gate transistors may be used. A semiconductor material used for the transistors is not particularly limited, and for example, silicon, germanium, silicon carbide, gallium nitride, or the like can be used. Alternatively, an oxide semiconductor containing at least one of indium, gallium, and zinc, such as an In—Ga—Zn-based metal oxide, may be used.

[0334] There is no particular limitation on the crystallinity of a semiconductor material used for the transistors, and either an amorphous semiconductor or a semiconductor having crystallinity (a microcrystalline semiconductor, a polycrystalline semiconductor, a single crystal semiconductor, or a semiconductor partly including crystal regions) can be used. It is preferable to use a semiconductor having crystallinity, in which case degradation of transistor characteristics can be inhibited.

[0335] Here, an oxide semiconductor is preferably used for semiconductor devices such as the transistors provided in the pixels and the driver circuits and transistors used for touch sensors described later, and the like. In particular, an oxide semiconductor having a wider band gap than silicon is preferably used. When an oxide semiconductor having a wider band gap than silicon is used, off-state current of the transistors can be reduced.

[0336] The oxide semiconductor preferably contains at least indium (In) or zinc (Zn). Further preferably, the oxide semiconductor contains an oxide represented by an In-M-Zn-based oxide (M represents a metal such as Al, Ti, Ga, Ge, Y, Zr, Sn, La, Ce, or Hf).

[0337] As a semiconductor layer, it is particularly preferable to use an oxide semiconductor film including a plurality of crystal parts whose c-axes are aligned perpendicular to a surface on which the semiconductor layer is formed or the top surface of the semiconductor layer and in which the adjacent crystal parts have no grain boundary.

[0338] The use of such materials for the semiconductor layer makes it possible to provide a highly reliable transistor in which a change in the electrical characteristics is suppressed.

[0339] Charge accumulated in a capacitor through a transistor including the above-described semiconductor layer can be held for a long time because of the low off-state current of the transistor. When such a transistor is used in a pixel, operation of a driver circuit can be stopped

while a gray scale of an image in each display region is maintained. As a result, an electronic appliance with extremely low power consumption can be obtained.

[0340] For stable characteristics of the transistor and the like, a base film is preferably provided. The base film can be formed with a single-layer structure or a stacked-layer structure using an inorganic insulating film such as a silicon oxide film, a silicon nitride film, a silicon oxynitride film, or a silicon nitride oxide film. The base film can be formed by a sputtering method, a chemical vapor deposition (CVD) method (e.g., a plasma CVD method, a thermal CVD method, or a metal organic CVD (MOCVD) method), an atomic layer deposition (ALD) method, a coating method, a printing method, or the like. Note that the base film is not necessarily provided.

[0341] Note that an FET **623** is illustrated as a transistor formed in the driver circuit portion **601**. In addition, the driver circuit may be formed with any of a variety of circuits such as a CMOS circuit, a PMOS circuit, or an NMOS circuit. Although a driver integrated type in which the driver circuit is formed over the substrate is described in this embodiment, the driver circuit is not necessarily formed over the substrate, and can be formed outside.

[0342] The pixel portion **602** includes a plurality of pixels including a switching FET **611**, a current controlling FET **612**, and a first electrode **613** electrically connected to a drain of the current controlling FET **612**. One embodiment of the present invention is not limited to the structure, and the pixel portion **602** may include three or more FETs and a capacitor in combination.

[0343] Note that an insulator **614** is formed to cover an end portion of the first electrode **613**. Here, the insulator **614** can be formed using a positive photosensitive acrylic resin film.

[0344] In order to improve coverage with an organic compound layer or the like which is formed later, the insulator **614** is formed to have a curved surface with curvature at its upper or lower end portion. For example, in the case where a positive photosensitive acrylic resin is used as a material of the insulator **614**, only the upper end portion of the insulator **614** preferably has a curved surface with a curvature radius (0.2 μm to 3 μm). For the insulator **614**, either a negative photosensitive resin or a positive photosensitive resin can be used.

[0345] An organic compound layer **616** and a second electrode **617** are formed over the first electrode **613**. Here, as a material used for the first electrode **613** functioning as an anode, a material having a high work function is preferably used. For example, a single-layer film of an ITO film, an indium tin oxide film including silicon, an indium oxide film including zinc oxide at 2 wt % to 20 wt %, a titanium nitride film, a chromium film, a tungsten film, a Zn film, a Pt film, or the like, a stack of a titanium nitride film and a film including aluminum as its main component, a stack of three layers of a titanium nitride film, a film including aluminum as its main component, and a titanium nitride film, or the like can be used. The stacked-layer structure enables low wiring resistance, favorable ohmic contact, and a function as an anode.

[0346] The organic compound layer **616** is formed by any of a variety of methods such as an evaporation method using an evaporation mask, an ink-jet method, and a spin coating method. The organic compound layer **616** has the structure described in Embodiment 1. As another material included in the organic compound layer **616**, a low molecular compound or a high molecular compound (including an oligomer or a dendrimer) may be used.

[0347] As a material used for the second electrode **617**, which is formed over the organic compound layer **616** and functions as a cathode, a material having a low work function (e.g., Al, Mg, Li, and Ca, or an alloy or a compound thereof, such as MgAg, MgIn, and AlLi) is preferably used. In the case where light generated in the organic compound layer **616** is transmitted through the second electrode **617**, a stack of a thin metal film and a transparent conductive film (e.g., ITO, indium oxide containing zinc oxide at 2 wt % to 20 wt %, indium tin oxide containing silicon, or zinc oxide (ZnO)) is preferably used for the second electrode **617**.

[0348] Note that the light-emitting device is formed with the first electrode **613**, the organic compound layer **616**, and the second electrode **617**. The light-emitting device is the light-emitting device described in Embodiment 1. In the display device of this embodiment, the pixel portion,

which includes a plurality of light-emitting devices may include both the light-emitting device described in Embodiment 1 and a light-emitting device having a different structure.

[0349] The sealing substrate **604** is bonded to the element substrate **610** with the sealing material **605**, so that a light-emitting device **618** is provided in the space **607** surrounded by the element substrate **610**, the sealing substrate **604**, and the sealing material **605**. The space **607** may be filled with a filler, or may be filled with an inert gas (such as nitrogen or argon), or the sealing material. It is preferable that the sealing substrate be provided with a recessed portion and a drying agent be provided in the recessed portion, in which case deterioration due to the influence of moisture can be suppressed.

[0350] An epoxy-based resin or glass frit is preferably used for the sealing material **605**. It is desirable that such a material not be permeable to moisture or oxygen as much as possible. As the sealing substrate **604**, a glass substrate, a quartz substrate, or a plastic substrate formed of fiber reinforced plastic (FRP), polyvinyl fluoride (PVF), polyester, an acrylic resin, or the like can be used.

[0351] Although not illustrated in FIG. 3B, a protective film may be provided over the second electrode **617**. As the protective film, an organic resin film or an inorganic insulating film may be formed. The protective film may be formed so as to cover an exposed portion of the sealing material **605**. The protective film may be provided so as to cover surfaces and side surfaces of the pair of substrates and exposed side surfaces of a sealing layer, an insulating layer, and the like.

[0352] The protective film can be formed using a material that is less likely to transmit an impurity such as water. Thus, diffusion of an impurity such as water from the outside into the inside can be effectively suppressed.

[0353] As a material for the protective film, an oxide, a nitride, a fluoride, a sulfide, a ternary compound, a metal, a polymer, or the like can be used. For example, the material may contain aluminum oxide, hafnium oxide, hafnium silicate, lanthanum oxide, silicon oxide, strontium titanate, tantalum oxide, titanium oxide, zinc oxide, niobium oxide, zirconium oxide, tin oxide, yttrium oxide, cerium oxide, scandium oxide, erbium oxide, vanadium oxide, indium oxide, aluminum nitride, hafnium nitride, silicon nitride, tantalum nitride, titanium nitride, niobium nitride, molybdenum nitride, zirconium nitride, gallium nitride, a nitride containing titanium and aluminum, an oxide containing titanium and aluminum, an oxide containing aluminum and zinc, a sulfide containing manganese and zinc, a sulfide containing cerium and strontium, an oxide containing erbium and aluminum, an oxide containing yttrium and zirconium, or the like.

[0354] The protective film is preferably formed using a film formation method with favorable step coverage. One such method is an atomic layer deposition (ALD) method. A material that can be deposited by an ALD method is preferably used for the protective film. A dense protective film having reduced defects such as cracks or pinholes or a uniform thickness can be formed by an ALD method. Furthermore, damage caused to a process member in forming the protective film can be reduced.

[0355] By an ALD method, a uniform protective film with few defects can be formed even on, for example, a surface with a complex uneven shape or upper, side, and lower surfaces of a touch panel.

[0356] As described above, the display device manufactured using the light-emitting device described in Embodiment 1 can be obtained.

[0357] The display device in this embodiment is manufactured using the light-emitting device described in Embodiment 1 and thus can have favorable characteristics. Specifically, since the light-emitting device described in Embodiment 1 has high emission efficiency, the display device can achieve low power consumption. Since the light-emitting device described in Embodiment 1 has high reliability, the display device can be highly reliable. In addition, since the light-emitting device described in Embodiment 1 can have favorable chromaticity and high color purity, the display device can achieve high display quality.

[0358] This embodiment can be freely combined with any of the other embodiments.

Embodiment 3

[0359] As illustrated in FIGS. **4A** and **4B**, a plurality of light-emitting devices **130** are formed over the insulating layer **175** to constitute a display device. In this embodiment, the display device of another embodiment of the present invention will be described in detail.

[0360] A display device **100** includes a pixel portion **177** in which a plurality of pixels **178** are arranged in a matrix. The pixel **178** includes a subpixel **110R**, a subpixel **110G**, and a subpixel **110B**.

[0361] In this specification and the like, for example, description common to the subpixels **110R**, **110G**, and **110B** is sometimes made using the collective term “subpixel **110**”. As for other components that are distinguished from each other using letters of the alphabet, matters common to the components are sometimes described using reference numerals excluding the letters of the alphabet.

[0362] The subpixel **110R** emits red light, the subpixel **110G** emits green light, and the subpixel **110B** emits blue light. Thus, an image can be displayed on the pixel portion **177**. Note that in this embodiment, three colors of red (R), green (G), and blue (B) are given as examples of colors of light emitted by the subpixels; however, subpixels of a different combination of colors may be employed. The number of subpixels is not limited to three, and may be four or more. Examples of four subpixels include subpixels emitting light of four colors of R, G, B, and white (W), subpixels emitting light of four colors of R, G, B, and Y, and four subpixels emitting light of R, G, and B and infrared light (IR).

[0363] In this specification and the like, the row direction and the column direction are sometimes referred to as the X direction and the Y direction, respectively. The X direction and the Y direction intersect with each other and are perpendicular to each other, for example.

[0364] FIG. **4A** illustrates an example where subpixels of different colors are arranged in the X direction and subpixels of the same color are arranged in the Y direction. Note that subpixels of different colors may be arranged in the Y direction, and subpixels of the same color may be arranged in the X direction.

[0365] Outside the pixel portion **177**, a connection portion **140** is provided and a region **141** may also be provided. In the case where the region **141** is provided, the region **141** is provided between the pixel portion **177** and the connection portion **140**. In the case where the region **141** is provided, an organic compound layer is provided in the region **141**. A conductive layer **151C** is provided in the connection portion **140**.

[0366] Although FIG. **4A** illustrates an example where the region **141** and the connection portion **140** are positioned on the right side of the pixel portion **177**, the positions of the region **141** and the connection portion **140** are not particularly limited. The number of the regions **141** and the number of the connection portions **140** can each be one or more.

[0367] FIG. **4B** is an example of a cross-sectional view along the dashed-dotted line A1-A2 in FIG. **4A**. As illustrated in FIG. **4B**, the display device **100** includes an insulating layer **171**, a conductive layer **172** over the insulating layer **171**, an insulating layer **173** over the insulating layer **171** and the conductive layer **172**, an insulating layer **174** over the insulating layer **173**, and the insulating layer **175** over the insulating layer **174**. The insulating layer **171** is provided over a substrate (not illustrated). An opening reaching the conductive layer **172** is provided in the insulating layers **175**, **174**, and **173**, and a plug **176** is provided to fill the opening.

[0368] In the pixel portion **177**, the light-emitting device **130** is provided over the insulating layer **175** and the plug **176**. A protective layer **131** is provided to cover the light-emitting device **130**. A substrate **120** is bonded to the protective layer **131** with a resin layer **122**. An inorganic insulating layer **125** and an insulating layer **127** over the inorganic insulating layer **125** are preferably provided between the adjacent light-emitting devices **130**.

[0369] Although FIG. **4B** illustrates cross sections of a plurality of inorganic insulating layers **125**

and a plurality of insulating layers **127**, the inorganic insulating layers **125** are preferably connected to each other and the insulating layers **127** are preferably connected to each other when the display device **100** is seen from above.

[0370] In FIG. **4B**, a light-emitting device **130R**, a light-emitting device **130G**, and a light-emitting device **130B** are each illustrated as the light-emitting device **130**. The light-emitting devices **130R**, **130G**, and **130B** emit light of different colors. For example, the light-emitting device **130R** can emit red light, the light-emitting device **130G** can emit green light, and the light-emitting device **130B** can emit blue light. Alternatively, the light-emitting device **130R**, the light-emitting device **130G**, or the light-emitting device **130B** may emit visible light of another color or infrared light.

[0371] The display device of one embodiment of the present invention can be, for example, a top-emission display device where light is emitted in the direction opposite to a substrate over which light-emitting devices are formed. Note that the display device of one embodiment of the present invention may be of a bottom emission type.

[0372] The light-emitting device **130R** includes a first electrode **101R** (pixel electrode) including a conductive layer **151R** and a conductive layer **152R**, an organic compound layer **103R** over the first electrode, a common layer **104** over the organic compound layer **103R**, and the second electrode **102** (common electrode) over the common layer **104**. Although the common layer **104** is not necessarily provided, it is preferable to provide the common layer **104** to reduce damage to the organic compound layer **103R** during processing.

[0373] The light-emitting device **130G** includes a first electrode **101G** (pixel electrode) including a conductive layer **151G** and a conductive layer **152G**, an organic compound layer **103G** over the first electrode, the common layer **104** over the organic compound layer **103G**, and the second electrode **102** (common electrode) over the common layer **104**. Although the common layer **104** is not necessarily provided, it is preferable to provide the common layer **104** to reduce damage to the organic compound layer **103G** during processing.

[0374] The light-emitting device **130B** has a structure as described in Embodiment 1. The light-emitting device **130B** includes a first electrode **101B** (pixel electrode) including a conductive layer **151B** and a conductive layer **152B**, an organic compound layer **103B** over the first electrode, the common layer **104** over the organic compound layer **103B**, and the second electrode **102** (common electrode) over the common layer **104**. Although the common layer **104** is not necessarily provided, it is preferable to provide the common layer **104** to reduce damage to the organic compound layer **103B** during processing. Furthermore, in the case where the common layer **104** is provided, a stack of the organic compound layer **103B** and the common layer **104** corresponds to the organic compound layer **103** described in Embodiment 1; in the case where the common layer **104** is not provided, the organic compound layer **103B** corresponds to the organic compound layer **103** described in Embodiment 1.

[0375] Note that the common layer **104** is preferably an electron-transport layer. In the case where the common layer **104** is an electron-transport layer, it is preferable that the electron-transport layer have a stacked-layer structure, and it is further preferable that, among the stacked layers, a layer on the second electrode side be the common layer **104** and a layer on the light-emitting layer side be the organic compound layer **103**.

[0376] The light-emitting devices **130R** and **130G** are manufactured through a photolithography process.

[0377] In the light-emitting device **130**, one of the pixel electrode and the common electrode functions as an anode and the other functions as a cathode. Hereinafter, description is made on the assumption that the pixel electrode functions as the anode and the common electrode functions as the cathode unless otherwise specified.

[0378] The organic compound layers **103R**, **103G**, and **103B** are island-shaped layers that are independent of each other on a light-emitting device basis or on an emission color basis. Providing the island-shaped organic compound layer **103** in each of the light-emitting devices **130** can inhibit

leakage current between the adjacent light-emitting devices **130** even in a high-resolution display device. This can prevent crosstalk, so that a display device with extremely high contrast can be obtained. Specifically, a display device having high current efficiency at low luminance can be obtained.

[0379] The island-shaped organic compound layer **103** is formed by forming an organic compound film and processing the organic compound film by a photolithography method.

[0380] The organic compound layer **103** is preferably provided to cover the top surface and the side surface of the first electrode (pixel electrode) of the light-emitting device **130**. In this case, the aperture ratio of the display device **100** can be easily increased as compared to the structure where an end portion of the organic compound layer **103** is positioned inward from an end portion of the pixel electrode. Covering the side surface of the pixel electrode of the light-emitting device **130** with the organic compound layer **103** can inhibit the pixel electrode from being in contact with the second electrode **102**; hence, a short circuit of the light-emitting device **130** can be inhibited.

[0381] In the display device of one embodiment of the present invention, the first electrode (pixel electrode) of the light-emitting device preferably has a stacked-layer structure. For example, in the example illustrated in FIG. **4B**, the first electrode of the light-emitting device **130** is a stack of the conductive layer **151** and the conductive layer **152**.

[0382] A metal material can be used for the conductive layer **151**, for example. Specifically, it is possible to use a metal such as aluminum (Al), titanium (Ti), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), gallium (Ga), zinc (Zn), indium (In), tin (Sn), molybdenum (Mo), tantalum (Ta), tungsten (W), palladium (Pd), gold (Au), platinum (Pt), silver (Ag), yttrium (Y), or neodymium (Nd) or an alloy containing an appropriate combination of any of these metals, for example.

[0383] For the conductive layer **152**, an oxide containing one or more selected from indium, tin, zinc, gallium, titanium, aluminum, and silicon can be used. For example, it is preferable to use a conductive oxide containing one or more of indium oxide, indium tin oxide, indium zinc oxide, zinc oxide, zinc oxide containing gallium, titanium oxide, indium zinc oxide containing gallium, indium zinc oxide containing aluminum, indium tin oxide containing silicon, indium zinc oxide containing silicon, and the like. In particular, indium tin oxide containing silicon can be suitably used for the conductive layer **152** because of having a work function higher than or equal to 4.0 eV, for example.

[0384] The conductive layer **151** and the conductive layer **152** may each be a stack of a plurality of layers including different materials. In that case, the conductive layer **151** may include a layer formed using a material that can be used for the conductive layer **152**, such as a conductive oxide. Furthermore, the conductive layer **152** may include a layer formed using a material that can be used for the conductive layer **151**, such as a metal material. In the case where the conductive layer **151** is a stack of two or more layers, for example, a layer in contact with the conductive layer **152** can be formed using a material that can be used for the conductive layer **152**.

[0385] Next, an exemplary method for manufacturing the display device **100** having the structure illustrated in FIG. **4A** is described with reference to FIGS. **5A** to **5E**, FIGS. **6A** and **6B**, FIG. **7A** to **7D**, FIGS. **8A** to **8C**, FIGS. **9A** to **9C**, and FIGS. **10A** to **10C**.

Manufacturing Method Example 1

[0386] Thin films included in the display device (e.g., insulating films, semiconductor films, and conductive films) can be formed by a sputtering method, a chemical vapor deposition (CVD) method, a vacuum evaporation method, a pulsed laser deposition (PLD) method, an ALD method, or the like.

[0387] Thin films included in the display device (e.g., insulating films, semiconductor films, and conductive films) can also be formed by a wet process such as spin coating, dipping, spray coating, ink-jetting, dispensing, screen printing, offset printing, doctor blade coating, slit coating, roll coating, curtain coating, or knife coating.

[0388] Thin films included in the display device can be processed by a photolithography method, for example.

[0389] As light used for exposure in the photolithography method, for example, light with an i-line (wavelength: 365 nm), light with a g-line (wavelength: 436 nm), light with an h-line (wavelength: 405 nm), or light in which the i-line, the g-line, and the h-line are mixed can be used. Alternatively, ultraviolet rays, KrF laser light, ArF laser light, or the like can be used. Exposure may be performed by liquid immersion exposure technique. As the light for exposure, extreme ultraviolet (EUV) light or X-rays may also be used. Furthermore, instead of the light used for the exposure, an electron beam can also be used.

[0390] For etching of thin films, a dry etching method, a wet etching method, a sandblast method, or the like can be used.

[0391] First, as illustrated in FIG. 5A, the insulating layer **171** is formed over a substrate (not illustrated). Next, the conductive layer **172** and a conductive layer **179** are formed over the insulating layer **171**, and the insulating layer **173** is formed over the insulating layer **171** so as to cover the conductive layer **172** and the conductive layer **179**. Then, the insulating layer **174** is formed over the insulating layer **173**, and the insulating layer **175** is formed over the insulating layer **174**.

[0392] As the substrate, a substrate that has heat resistance high enough to withstand at least heat treatment performed later can be used. For example, it is possible to use a glass substrate; a quartz substrate; a sapphire substrate; a ceramic substrate; an organic resin substrate; or a semiconductor substrate such as a single crystal semiconductor substrate or a polycrystalline semiconductor substrate of silicon, silicon carbide, or the like, a compound semiconductor substrate of silicon germanium or the like, or an SOI substrate.

[0393] Next, as illustrated in FIG. 5A, an opening reaching the conductive layer **172** is formed in the insulating layers **175**, **174**, and **173**. Then, the plug **176** is formed to fill the opening.

[0394] Subsequently, as illustrated in FIG. 5A, a conductive film **151f** to be the conductive layers **151R**, **151G**, **151B**, and **151C** and a conductive film **152f** to be the conductive layers **152R**, **152G**, **152B**, and **152C** are formed over the plug **176** and the insulating layer **175**. A metal material can be used for the conductive film **151f**, for example. For the conductive film **152f**, an oxide containing one or more selected from indium, tin, zinc, gallium, titanium, aluminum, and silicon can be used, for example.

[0395] Then, as illustrated in FIG. 5A, a resist mask **191** is formed over the conductive film **152f**. The resist mask **191** can be formed by application of a photosensitive material (photoresist), light exposure, and development.

[0396] Subsequently, as illustrated in FIG. 5B, the conductive films **151f** and **152f** in a region not overlapping with the resist mask **191** are removed, for example. In this manner, the conductive layers **151** and **152** are formed.

[0397] Next, the resist mask **191** is removed as illustrated in FIG. 5C. The resist mask **191** can be removed by ashing using oxygen plasma, for example.

[0398] Then, as illustrated in FIG. 5D, an insulating film **156f** to be an insulating layer **156R**, an insulating layer **156G**, an insulating layer **156B**, and an insulating layer **156C** is formed over the conductive layers **152R**, **152G**, **152B**, and **152C** and the insulating layer **175**.

[0399] As the insulating film **156f**, an inorganic insulating film such as an oxide insulating film, a nitride insulating film, an oxynitride insulating film, or a nitride oxide insulating film, e.g., a silicon oxynitride film, can be used.

[0400] Subsequently, as illustrated in FIG. 5E, the insulating film **156f** is processed to form the insulating layers **156R**, **156G**, **156B**, and **156C**.

[0401] Next, as illustrated in FIG. 6A, an organic compound film **103Rf** is formed over the conductive layers **152R**, **152G**, and **152B** and the insulating layer **175**. As illustrated in FIG. 6A, the organic compound film **103Rf** is not formed over the conductive layer **152C**.

[0402] Then, as illustrated in FIG. 6A, a sacrificial film **158Rf** and a mask film **159Rf** are formed.

[0403] Providing the sacrificial film **158Rf** over the organic compound film **103Rf** can reduce damage to the organic compound film **103Rf** in the manufacturing process of the display device, resulting in an increase in the reliability of the light-emitting device.

[0404] As the sacrificial film **158Rf**, a film that is highly resistant to the process conditions for the organic compound film **103Rf**, specifically, a film having high etching selectivity with respect to the organic compound film **103Rf** is used. For the mask film **159Rf**, a film having high etching selectivity with respect to the sacrificial film **158Rf** is used.

[0405] The sacrificial film **158Rf** and the mask film **159Rf** are formed at a temperature lower than the upper temperature limit of the organic compound film **103Rf**. The typical substrate temperatures in formation of the sacrificial film **158Rf** and the mask film **159Rf** are each higher than or equal to 100° C. and lower than or equal to 200° C., preferably higher than or equal to 100° C. and lower than or equal to 150° C., further preferably higher than or equal to 100° C. and lower than or equal to 120° C. The light-emitting device of one embodiment of the present invention includes the first organic compound, and thus enables a display device with high display quality even when manufactured through a heating process at a higher temperature.

[0406] The sacrificial film **158Rf** and the mask film **159Rf** are preferably films that can be removed by a wet etching method or a dry etching method.

[0407] Note that the sacrificial film **158Rf** formed over and in contact with the organic compound film **103Rf** is preferably formed by a formation method that is less likely to damage the organic compound film **103Rf** than a formation method of the mask film **159Rf**. For example, the sacrificial film **158Rf** is preferably formed by an ALD method or a vacuum evaporation method rather than a sputtering method.

[0408] As each of the sacrificial film **158Rf** and the mask film **159Rf**, one or more of a metal film, an alloy film, a metal oxide film, a semiconductor film, an organic insulating film, an inorganic insulating film, and the like can be used, for example.

[0409] For each of the sacrificial film **158Rf** and the mask film **159Rf**, it is possible to use a metal material such as gold, silver, platinum, magnesium, nickel, tungsten, chromium, molybdenum, iron, cobalt, copper, palladium, titanium, aluminum, yttrium, zirconium, or tantalum or an alloy material containing any of the metal materials, for example. It is particularly preferable to use a low-melting-point material such as aluminum or silver. It is preferable to use a metal material that can block ultraviolet rays for one or both of the sacrificial film **158Rf** and the mask film **159Rf**, in which case the organic compound film **103Rf** can be inhibited from being irradiated with ultraviolet rays in light exposure for patterning and deterioration of the organic compound film **103Rf** can be inhibited.

[0410] The sacrificial film **158Rf** and the mask film **159Rf** can each be formed using a metal oxide such as In—Ga—Zn oxide, indium oxide, In—Zn oxide, In—Sn oxide, indium titanium oxide (In—Ti oxide), indium tin zinc oxide (In—Sn—Zn oxide), indium titanium zinc oxide (In—Ti—Zn oxide), indium gallium tin zinc oxide (In—Ga—Sn—Zn oxide), or indium tin oxide containing silicon.

[0411] In the above metal oxide, in place of gallium, an element M (M is one or more of aluminum, silicon, boron, yttrium, copper, vanadium, beryllium, titanium, iron, nickel, germanium, zirconium, molybdenum, lanthanum, cerium, neodymium, hafnium, tantalum, tungsten, and magnesium) may be used.

[0412] The sacrificial film **158Rf** and the mask film **159Rf** are preferably formed using a semiconductor material such as silicon or germanium for excellent compatibility with a semiconductor manufacturing process. Alternatively, a compound containing the above semiconductor material can be used.

[0413] As each of the sacrificial film **158Rf** and the mask film **159Rf**, any of a variety of inorganic insulating films can be used. In particular, an oxide insulating film is preferable because its

adhesion to the organic compound film **103Rf** is higher than that of a nitride insulating film.

[0414] Subsequently, a resist mask **190R** is formed as illustrated in FIG. **6A**. The resist mask **190R** can be formed by application of a photosensitive material (photoresist), light exposure, and development.

[0415] The resist mask **190R** is provided at a position overlapping with the conductive layer **152R**. The resist mask **190R** is preferably provided also at a position overlapping with the conductive layer **152C**. This can inhibit the conductive layer **152C** from being damaged during the process of manufacturing the display device.

[0416] Next, as illustrated in FIG. **6B**, part of the mask film **159Rf** is removed using the resist mask **190R**, whereby a mask layer **159R** is formed. The mask layer **159R** remains over the conductive layers **152R** and **152C**. After that, the resist mask **190R** is removed. Then, part of the sacrificial film **158Rf** is removed using the mask layer **159R** as a mask (also referred to as a hard mask), whereby a sacrificial layer **158R** is formed.

[0417] The use of a wet etching method can reduce damage to the organic compound film **103Rf** in processing of the sacrificial film **158Rf** and the mask film **159Rf**, as compared to the case of using a dry etching method. In the case of using a wet etching method, it is preferable to use an alkaline aqueous solution such as a developer or a tetramethylammonium hydroxide (TMAH) aqueous solution, or an acid aqueous solution such as dilute hydrofluoric acid, oxalic acid, phosphoric acid, acetic acid, nitric acid, or a chemical solution containing a mixed solution of any of these acids, for example.

[0418] In the case of using a dry etching method to process the sacrificial film **158Rf**, deterioration of the organic compound film **103Rf** can be inhibited by not using a gas containing oxygen as the etching gas.

[0419] The resist mask **190R** can be removed by a method similar to that for the resist mask **191**.

[0420] Next, as illustrated in FIG. **6B**, the organic compound film **103Rf** is processed to form the organic compound layer **103R**. For example, part of the organic compound film **103Rf** is removed using the mask layer **159R** and the sacrificial layer **158R** as a hard mask, whereby the organic compound layer **103R** is formed.

[0421] Accordingly, as illustrated in FIG. **6B**, the stacked-layer structure of the organic compound layer **103R**, the sacrificial layer **158R**, and the mask layer **159R** remains over the conductive layer **152R**. The conductive layers **152G** and **152B** are exposed.

[0422] The organic compound film **103Rf** is preferably processed by anisotropic etching. Anisotropic dry etching is particularly preferable. Alternatively, wet etching may be used.

[0423] In the case of using a dry etching method, deterioration of the organic compound film **103Rf** can be inhibited by not using a gas containing oxygen as the etching gas.

[0424] A gas containing oxygen may be used as the etching gas. When the etching gas contains oxygen, the etching rate can be increased. Thus, the etching can be performed under a low-power condition while an adequately high etching rate is maintained. Accordingly, damage to the organic compound film **103Rf** can be reduced. Furthermore, a defect such as attachment of a reaction product generated during the etching can be inhibited.

[0425] In the case of using a dry etching method, it is preferable to use a gas containing at least one of H.sub.2, CF.sub.4, C.sub.4F.sub.8, SF.sub.6, CHF.sub.3, Cl.sub.2, H.sub.2O, BCl.sub.3, and a Group 18 element such as He or Ar as the etching gas, for example. Alternatively, a gas containing oxygen and at least one of the above is preferably used as the etching gas. Alternatively, an oxygen gas may be used as the etching gas.

[0426] Then, as illustrated in FIG. **7A**, an organic compound film **103Gf** to be the organic compound layer **103G** is formed.

[0427] The organic compound film **103Gf** can be formed by a method similar to that for forming the organic compound film **103Rf**. The organic compound film **103Gf** can have a structure similar to that of the organic compound film **103Rf**.

[0428] Subsequently, a sacrificial film **158Gf** and a mask film **159Gf** are formed in this order as illustrated in FIG. 7A. After that, a resist mask **190G** is formed. The materials and the formation methods of the sacrificial film **158Gf** and the mask film **159Gf** are similar to those for the sacrificial film **158Rf** and the mask film **159Rf**. The material and the formation method of the resist mask **190G** are similar to those for the resist mask **190R**.

[0429] The resist mask **190G** is provided at a position overlapping with the conductive layer **152G**.

[0430] Subsequently, as illustrated in FIG. 7B, part of the mask film **159Gf** is removed using the resist mask **190G**, whereby a mask layer **159G** is formed. The mask layer **159G** remains over the conductive layer **152G**. After that, the resist mask **190G** is removed. Then, part of the sacrificial film **158Gf** is removed using the mask layer **159G** as a mask, whereby a sacrificial layer **158G** is formed. Next, the organic compound film **103Gf** is processed to form the organic compound layer **103G**.

[0431] Then, an organic compound film **103Bf** is formed as illustrated in FIG. 7C.

[0432] The organic compound film **103Bf** can be formed by a method similar to that for forming the organic compound film **103Rf**. The organic compound film **103Bf** can have a structure similar to that of the organic compound film **103Rf**.

[0433] Subsequently, a sacrificial film **158Bf** and a mask film **159Bf** are formed in this order as illustrated in FIG. 7C. After that, a resist mask **190B** is formed. The materials and the formation methods of the sacrificial film **158Bf** and the mask film **159Bf** are similar to those for the sacrificial film **158Rf** and the mask film **159Rf**. The material and the formation method of the resist mask **190B** are similar to those for the resist mask **190R**.

[0434] The resist mask **190B** is provided at a position overlapping with the conductive layer **152B**.

[0435] Subsequently, as illustrated in FIG. 7D, part of the mask film **159Bf** is removed using the resist mask **190B**, whereby a mask layer **159B** is formed. The mask layer **159B** remains over the conductive layer **152B**. After that, the resist mask **190B** is removed. Then, part of the sacrificial film **158Bf** is removed using the mask layer **159B** as a mask, whereby a sacrificial layer **158B** is formed. Next, the organic compound film **103Bf** is processed to form the organic compound layer **103B**. For example, part of the organic compound film **103Bf** is removed using the mask layer **159B** and the sacrificial layer **158B** as a hard mask, whereby the organic compound layer **103B** is formed.

[0436] Accordingly, as illustrated in FIG. 7D, the stacked-layer structure of the organic compound layer **103B**, the sacrificial layer **158B**, and the mask layer **159B** remains over the conductive layer **152B**. The mask layers **159R** and **159G** are exposed.

[0437] Note that the side surfaces of the organic compound layers **103R**, **103G**, and **103B** are preferably perpendicular or substantially perpendicular to their formation surfaces. For example, the angle between the formation surfaces and these side surfaces is preferably greater than or equal to 60° and less than or equal to 90°.

[0438] The distance between two adjacent layers among the organic compound layers **103R**, **103G**, and **103B**, which are formed by a photolithography method as described above, can be reduced to less than or equal to 8 μm, less than or equal to 5 μm, less than or equal to 3 μm, less than or equal to 2 μm, or less than or equal to 1 μm. Here, the distance can be specified, for example, by a distance between facing end portions of two adjacent layers among the organic compound layers **103R**, **103G**, and **103B**. Reducing the distance between the island-shaped organic compound layers makes it possible to provide a display device having high resolution and a high aperture ratio. In addition, the distance between the first electrodes of adjacent light-emitting devices can also be reduced to for example, less than or equal to 10 μm, less than or equal to 8 μm, less than or equal to 5 μm, less than or equal to 3 μm, or less than or equal to 2 μm. Note that the distance between the first electrodes of adjacent light-emitting devices is preferably greater than or equal to 2 μm and less than or equal to 5 μm.

[0439] Next, as illustrated in FIG. 8A, the mask layers **159R**, **159G**, and **159B** are preferably

removed.

[0440] The step of removing the mask layers can be performed by a method similar to that for the step of processing the mask films. Specifically, by using a wet etching method, damage to the organic compound layer **103** at the time of removing the mask layers can be reduced as compared to the case of using a dry etching method.

[0441] The mask layers may be removed by being dissolved in a polar solvent such as water or an alcohol. Examples of an alcohol include ethyl alcohol, methyl alcohol, isopropyl alcohol (IPA), and glycerin.

[0442] After the mask layers are removed, drying treatment may be performed in order to remove water adsorbed on surfaces. For example, heat treatment in an inert gas atmosphere or a reduced-pressure atmosphere can be performed. The heat treatment can be performed at a substrate temperature higher than or equal to 50° C. and lower than or equal to 200° C., preferably higher than or equal to 60° C. and lower than or equal to 150° C., further preferably higher than or equal to 70° C. and lower than or equal to 120° C. The heat treatment is preferably performed in a reduced-pressure atmosphere, in which case drying at a lower temperature is possible.

[0443] Next, an inorganic insulating film **125f** is formed as illustrated in FIG. **8B**.

[0444] Then, as illustrated in FIG. **8C**, an insulating film **127f** to be the insulating layer **127** is formed over the inorganic insulating film **125f**.

[0445] The substrate temperature at the time of forming the inorganic insulating film **125f** and the insulating film **127f** is preferably higher than or equal to 60° C., higher than or equal to 80° C., higher than or equal to 100° C., or higher than or equal to 120° C. and lower than or equal to 200° C., lower than or equal to 180° C., lower than or equal to 160° C., lower than or equal to 150° C., or lower than or equal to 140° C.

[0446] As the inorganic insulating film **125f**, an insulating film having a thickness greater than or equal to 3 nm, greater than or equal to 5 nm, or greater than or equal to 10 nm and less than or equal to 200 nm, less than or equal to 150 nm, less than or equal to 100 nm, or less than or equal to 50 nm is preferably formed in the above-described range of the substrate temperature.

[0447] The inorganic insulating film **125f** is preferably formed by an ALD method, for example. An ALD method is preferably used, in which case film formation damage is reduced and a film with good coverage can be formed. As the inorganic insulating film **125f**, an aluminum oxide film is preferably formed by an ALD method, for example.

[0448] The insulating film **127f** is preferably formed by the aforementioned wet process. The insulating film **127f** is preferably formed by spin coating using a photosensitive material, for example, and specifically preferably formed using a photosensitive resin composition containing an acrylic resin.

[0449] Then, part of the insulating film **127f** is exposed to visible light or ultraviolet rays. The insulating layer **127** is formed in regions that are interposed between any two of the conductive layers **152R**, **152G**, and **152B** and around the conductive layer **152C**.

[0450] The width of the insulating layer **127** formed later can be controlled with the exposed region of the insulating film **127f**. In this embodiment, processing is performed such that the insulating layer **127** includes a portion overlapping with the top surface of the conductive layer **151**.

[0451] Light used for the exposure preferably includes the i-line (wavelength: 365 nm). Furthermore, light used for the exposure may include at least one of the g-line (wavelength: 436 nm) and the h-line (wavelength: 405 nm).

[0452] Next, as illustrated in FIG. **9A**, development is performed to remove the exposed region of the insulating film **127f**, whereby an insulating layer **127a** is formed.

[0453] Next, as illustrated in FIG. **9B**, etching treatment is performed using the insulating layer **127a** as a mask to remove part of the inorganic insulating film **125f** and reduce the thickness of part of the sacrificial layers **158R**, **158G**, and **158B**. Thus, the inorganic insulating layer **125** is formed under the insulating layer **127a**. Moreover, the surfaces of the thin portions of the sacrificial layers

158R, **158G**, and **158B** are exposed. Note that the etching treatment using the insulating layer **127a** as a mask may be hereinafter referred to as first etching treatment.

[0454] The first etching treatment can be performed by dry etching or wet etching. Note that the inorganic insulating film **125f** is preferably formed using a material similar to that for the sacrificial layers **158R**, **158G**, and **158B**, in which case the first etching treatment can be performed concurrently.

[0455] In the case of performing dry etching, a chlorine-based gas is preferably used. As the chlorine-based gas, one of Cl.sub.2, BCl.sub.3, SiCl.sub.4, CCl.sub.4, and the like or a mixture of two or more of them can be used. Moreover, one of an oxygen gas, a hydrogen gas, a helium gas, an argon gas, and the like or a mixture of two or more of them can be added as appropriate to the chlorine-based gas. By the dry etching, the thin regions of the sacrificial layers **158R**, **158G**, and **158B** can be formed with favorable in-plane uniformity.

[0456] As a dry etching apparatus, a dry etching apparatus including a high-density plasma source can be used. As the dry etching apparatus including a high-density plasma source, an inductively coupled plasma (ICP) etching apparatus can be used, for example. Alternatively, a capacitively coupled plasma (CCP) etching apparatus including parallel plate electrodes can be used.

[0457] The first etching treatment is preferably performed by wet etching. The use of wet etching can reduce damage to the organic compound layers **103R**, **103G**, and **103B**, as compared to the case of using dry etching. Wet etching can be performed using an alkaline solution, for example. For instance, TMAH, which is an alkaline solution, can be used for the wet etching of an aluminum oxide film. Alternatively, an acid solution containing fluoride can also be used. In this case, puddle wet etching can be performed. Note that the inorganic insulating film **125f** is preferably formed using a material similar to that for the sacrificial layers **158R**, **158G**, and **158B**, in which case the above etching treatment can be performed concurrently.

[0458] The sacrificial layers **158R**, **158G**, and **158B** are not removed completely by the first etching treatment, and the etching treatment is stopped when the thickness of the sacrificial layers **158R**, **158G**, and **158B** is reduced. The sacrificial layers **158R**, **158G**, and **158B** remain over the corresponding organic compound layers **103R**, **103G**, and **103B** in this manner, whereby the organic compound layers **103R**, **103G**, and **103B** can be prevented from being damaged by treatment in a later step.

[0459] Next, light exposure is preferably performed on the entire substrate so that the insulating layer **127a** is irradiated with visible light or ultraviolet rays. The energy density for the light exposure is preferably greater than 0 mJ/cm.sup.2 and less than or equal to 800 mJ/cm.sup.2, further preferably greater than 0 mJ/cm.sup.2 and less than or equal to 500 mJ/cm.sup.2. Performing such light exposure after the development can sometimes increase the degree of transparency of the insulating layer **127a**. In addition, it is sometimes possible to lower the substrate temperature required for subsequent heat treatment for changing the shape of the insulating layer **127a** into a tapered shape.

[0460] Here, when a barrier insulating layer against oxygen (e.g., an aluminum oxide film) exists as each of the sacrificial layers **158R**, **158G**, and **158B**, diffusion of oxygen to the organic compound layers **103R**, **103G**, and **103B** can be inhibited.

[0461] Then, heat treatment (also referred to as post-baking) is performed. The heat treatment can change the insulating layer **127a** into the insulating layer **127** having a tapered side surface (FIG. 9C). The heat treatment is performed at a temperature lower than the upper temperature limit of the organic compound layer. The heat treatment can be performed at a substrate temperature higher than or equal to 50° C. and lower than or equal to 200° C., preferably higher than or equal to 60° C. and lower than or equal to 150° C., further preferably higher than or equal to 70° C. and lower than or equal to 130° C. The heating atmosphere may be an air atmosphere or an inert gas atmosphere. Moreover, the heating atmosphere may be an atmospheric-pressure atmosphere or a reduced-pressure atmosphere. Accordingly, adhesion between the insulating layer **127** and the inorganic

insulating layer **125** can be improved, and corrosion resistance of the insulating layer **127** can be increased.

[0462] When the sacrificial layers **158R**, **158G**, and **158B** are not completely removed by the first etching treatment and the thinned sacrificial layers **158R**, **158G**, and **158B** are left, the organic compound layers **103R**, **103G**, and **103B** can be prevented from being damaged and deteriorating in the heat treatment. This can increase the reliability of the light-emitting devices.

[0463] Next, as illustrated in FIG. **10A**, etching treatment is performed using the insulating layer **127** as a mask to remove parts of the sacrificial layers **158R**, **158G**, and **158B**. Thus, openings are formed in the sacrificial layers **158R**, **158G**, and **158B**, and the top surfaces of the organic compound layers **103R**, **103G**, and **103B** and the conductive layer **152C** are exposed. Note that this etching treatment may be hereinafter referred to as second etching treatment.

[0464] An end portion of the inorganic insulating layer **125** is covered with the insulating layer **127**. FIG. **10A** illustrates an example where part of an end portion of the sacrificial layer **158G** (specifically a tapered portion formed by the first etching treatment) is covered with the insulating layer **127** and a tapered portion formed by the second etching treatment is exposed.

[0465] The second etching treatment is performed by wet etching. The use of wet etching can reduce damage to the organic compound layers **103R**, **103G**, and **103B**, as compared to the case of using dry etching. Wet etching can be performed using an alkaline solution or an acid solution, for example. An aqueous solution is preferably used in order that the organic compound layer **103** is not dissolved.

[0466] Next, as illustrated in FIG. **10B**, a common electrode **155** is formed over the organic compound layers **103R**, **103G**, and **103B**, the conductive layer **152C**, and the insulating layer **127**. The common electrode **155** can be formed by a sputtering method, a vacuum evaporation method, or the like.

[0467] Next, as illustrated in FIG. **10C**, the protective layer **131** is formed over the common electrode **155**. The protective layer **131** can be formed by a vacuum evaporation method, a sputtering method, a CVD method, an ALD method, or the like.

[0468] Then, the substrate **120** is bonded to the protective layer **131** using the resin layer **122**, so that the display device can be manufactured. In the method for manufacturing the display device of one embodiment of the present invention, the insulating layer **156** is formed to include a region overlapping with the side surface of the conductive layer **151** and the conductive layer **152** is formed to cover the conductive layer **151** and the insulating layer **156** as described above. This can increase the yield of the display device and inhibit generation of defects.

[0469] As described above, in the method for manufacturing the display device of one embodiment of the present invention, the island-shaped organic compound layers **103R**, **103G**, and **103B** are formed not by using a fine metal mask but by processing a film formed on the entire surface; thus, the island-shaped layers can be formed to have a uniform thickness. In addition, a high-resolution display device or a display device with a high aperture ratio can be obtained. Furthermore, even when the resolution or the aperture ratio is high and the distance between the subpixels is extremely short, the organic compound layers **103R**, **103G**, and **103B** can be inhibited from being in contact with each other in the adjacent subpixels. As a result, generation of leakage current between the subpixels can be inhibited. This can prevent crosstalk, so that a display device with extremely high contrast can be obtained. Moreover, even a display device that includes tandem light-emitting devices formed by a photolithography method can have favorable characteristics.

Embodiment 4

[0470] In this embodiment, a display device of one embodiment of the present invention will be described.

[0471] The display device in this embodiment can be a high-resolution display device. Thus, the display device in this embodiment can be used for display portions of information terminals (wearable devices) such as watch-type and bracelet-type information terminals and display portions

of wearable devices capable of being worn on a head, such as a VR device like a head mounted display (HMD) and a glasses-type AR device.

[0472] The display device in this embodiment can be a high-definition display device or a large-sized display device. Accordingly, the display device in this embodiment can be used for display portions of a digital camera, a digital video camera, a digital photo frame, a mobile phone, a portable game console, a portable information terminal, and an audio reproducing device, in addition to display portions of electronic appliances with a relatively large screen, such as a television device, desktop and notebook personal computers, a monitor of a computer and the like, digital signage, and a large game machine such as a pachinko machine.

[Display Module]

[0473] FIG. 11A is a perspective view of a display module **280**. The display module **280** includes a display device **100A** and an FPC **290**. Note that the display device included in the display module **280** is not limited to the display device **100A** and may be any of a display device **100B**, a display device **100C**, a display device **100D**, a display device **100D2**, a display device **100E**, and a display device **100E2** described later.

[0474] The display module **280** includes a substrate **291** and a substrate **292**. The display module **280** includes a display portion **281**. The display portion **281** is a region of the display module **280** where an image is displayed, and is a region where light emitted from pixels provided in a pixel portion **284** described later can be seen.

[0475] FIG. 11B is a perspective view schematically illustrating the structure on the substrate **291** side. Over the substrate **291**, a circuit portion **282**, a pixel circuit portion **283** over the circuit portion **282**, and the pixel portion **284** over the pixel circuit portion **283** are stacked. In addition, a terminal portion **285** for connection to the FPC **290** is included in a portion over the substrate **291** that does not overlap with the pixel portion **284**. The terminal portion **285** and the circuit portion **282** are electrically connected to each other through a wiring portion **286** formed of a plurality of wirings.

[0476] The pixel portion **284** includes a plurality of pixels **284a** arranged periodically. An enlarged view of one pixel **284a** is illustrated on the right side in FIG. 11B. The pixels **284a** can employ any of the structures described in the above embodiments.

[0477] The pixel circuit portion **283** includes a plurality of pixel circuits **283a** arranged periodically.

[0478] One pixel circuit **283a** is a circuit that controls driving of a plurality of elements included in one pixel **284a**.

[0479] The circuit portion **282** includes a circuit for driving the pixel circuits **283a** in the pixel circuit portion **283**. For example, the circuit portion **282** preferably includes one or both of a gate line driver circuit and a source line driver circuit. The circuit portion **282** may also include at least one of an arithmetic circuit, a memory circuit, a power supply circuit, and the like.

[0480] The FPC **290** functions as a wiring for supplying a video signal, a power supply potential, or the like to the circuit portion **282** from the outside. An IC may be mounted on the FPC **290**.

[0481] The display module **280** can have a structure in which one or both of the pixel circuit portion **283** and the circuit portion **282** are stacked below the pixel portion **284**; hence, the aperture ratio (effective display area ratio) of the display portion **281** can be significantly high.

[0482] Such a display module **280** has extremely high resolution, and thus can be suitably used for a VR device such as an HMD or a glasses-type AR device. For example, even in the case of a structure in which the display portion of the display module **280** is seen through a lens, pixels of the extremely-high-resolution display portion **281** included in the display module **280** are prevented from being recognized when the display portion is enlarged by the lens, so that display providing a high sense of immersion can be performed. Without being limited thereto, the display module **280** can be suitably used for electronic appliances including a relatively small display portion.

[Display Device **100A**]

[0483] The display device **100A** illustrated in FIG. **12A** includes a substrate **301**, the light-emitting devices **130R**, **130G**, and **130B**, a capacitor **240**, and a transistor **310**.

[0484] The substrate **301** corresponds to the substrate **291** in FIGS. **12A** and **12B**. The transistor **310** includes a channel formation region in the substrate **301**. As the substrate **301**, a semiconductor substrate such as a single crystal silicon substrate can be used, for example. The transistor **310** includes part of the substrate **301**, a conductive layer **311**, a low-resistance region **312**, an insulating layer **313**, and an insulating layer **314**. The conductive layer **311** functions as a gate electrode. The insulating layer **313** is positioned between the substrate **301** and the conductive layer **311** and functions as a gate insulating layer. The low-resistance region **312** is a region where the substrate **301** is doped with an impurity, and functions as a source or a drain. The insulating layer **314** is provided to cover the side surface of the conductive layer **311**.

[0485] An element isolation layer **315** is provided between two adjacent transistors **310** to be embedded in the substrate **301**.

[0486] An insulating layer **261** is provided to cover the transistor **310**, and the capacitor **240** is provided over the insulating layer **261**.

[0487] The capacitor **240** includes a conductive layer **241**, a conductive layer **245**, and an insulating layer **243** between the conductive layers **241** and **245**. The conductive layer **241** functions as one electrode of the capacitor **240**, the conductive layer **245** functions as the other electrode of the capacitor **240**, and the insulating layer **243** functions as a dielectric of the capacitor **240**.

[0488] The conductive layer **241** is provided over the insulating layer **261** and is embedded in an insulating layer **254**. The conductive layer **241** is electrically connected to one of the source and the drain of the transistor **310** through a plug **271** embedded in the insulating layer **261**. The insulating layer **243** is provided to cover the conductive layer **241**. The conductive layer **245** is provided in a region overlapping with the conductive layer **241** with the insulating layer **243** therebetween.

[0489] An insulating layer **255** is provided to cover the capacitor **240**. The insulating layer **174** is provided over the insulating layer **255**. The insulating layer **175** is provided over the insulating layer **174**. The light-emitting devices **130R**, **130G**, and **130B** are provided over the insulating layer **175**. An insulator is provided in regions between adjacent light-emitting devices.

[0490] The insulating layer **156R** is provided to include a region overlapping with the side surface of the conductive layer **151R**. The insulating layer **156G** is provided to include a region overlapping with the side surface of the conductive layer **151G**. The insulating layer **156B** is provided to include a region overlapping with the side surface of the conductive layer **151B**. The conductive layer **152R** is provided to cover the conductive layer **151R** and the insulating layer **156R**. The conductive layer **152G** is provided to cover the conductive layer **151G** and the insulating layer **156G**. The conductive layer **152B** is provided to cover the conductive layer **151B** and the insulating layer **156B**. The sacrificial layer **158R** is positioned over the organic compound layer **103R**. The sacrificial layer **158G** is positioned over the organic compound layer **103G**. The sacrificial layer **158B** is positioned over the organic compound layer **103B**.

[0491] Each of the conductive layers **151R**, **151G**, and **151B** is electrically connected to one of the source and the drain of the corresponding transistor **310** through a plug **256** embedded in the insulating layers **243**, **255**, **174**, and **175**, the conductive layer **241** embedded in the insulating layer **254**, and the plug **271** embedded in the insulating layer **261**. Any of a variety of conductive materials can be used for the plugs.

[0492] The protective layer **131** is provided over the light-emitting devices **130R**, **130G**, and **130B**. The substrate **120** is bonded to the protective layer **131** with the resin layer **122**. Embodiment 3 can be referred to for the details of the light-emitting device **130** and the components thereof up to the substrate **120**. The substrate **120** corresponds to the substrate **292** in FIG. **11A**.

[0493] FIG. **12B** illustrates a variation example of the display device **100A** illustrated in FIG. **12A**.

The display device illustrated in FIG. 12B includes a coloring layer 132R, a coloring layer 132G, and a coloring layer 132B, and each of the light-emitting devices 130 includes a region overlapping with one of the coloring layers 132R, 132G, and 132B. In the display device illustrated in FIG. 12B, the light-emitting device 130 can emit white light, for example. The coloring layer 132R, the coloring layer 132G, and the coloring layer 132B can transmit red light, green light, and blue light, respectively, for example.

[Display Device 100B]

[0494] FIG. 13 is a perspective view of the display device 100B, and FIG. 14 is a cross-sectional view of the display device 100C.

[0495] In the display device 100B, a substrate 352 and a substrate 351 are bonded to each other. In FIG. 13, the substrate 352 is denoted by a dashed line.

[0496] The display device 100B includes the pixel portion 177, the connection portion 140, a circuit 356, a wiring 355, and the like. FIG. 13 illustrates an example where an IC 354 and an FPC 353 are mounted on the display device 100B. Thus, the structure illustrated in FIG. 13 can be regarded as a display module including the display device 100B, the integrated circuit (IC), and the FPC. Here, a display device in which a substrate is equipped with a connector such as an FPC or mounted with an IC is referred to as a display module.

[0497] The connection portion 140 is provided outside the pixel portion 177. The number of connection portions 140 may be one or more. In the connection portion 140, a common electrode of a light-emitting device is electrically connected to a conductive layer, so that a potential can be supplied to the common electrode.

[0498] As the circuit 356, a scan line driver circuit can be used, for example.

[0499] The wiring 355 has a function of supplying a signal and power to the pixel portion 177 and the circuit 356. The signal and power are input to the wiring 355 from the outside through the FPC 353 or from the IC 354.

[0500] FIG. 13 illustrates an example where the IC 354 is provided over the substrate 351 by a chip on glass (COG) method, a chip on film (COF) method, or the like. An IC including a scan line driver circuit, a signal line driver circuit, or the like can be used as the IC 354, for example. Note that the display device 100B and the display module are not necessarily provided with an IC. Alternatively, the IC may be mounted on the FPC by a COF method, for example.

[0501] FIG. 14 illustrates the display device 100C as an example of cross sections of part of a region including the FPC 353, part of the circuit 356, part of the pixel portion 177, part of the connection portion 140, and part of a region including an end portion of the display device 100B in FIG. 13.

[Display Device 100C]

[0502] The display device 100C illustrated in FIG. 14 includes a transistor 201, a transistor 205, the light-emitting device 130R that emits red light, the light-emitting device 130G that emits green light, the light-emitting device 130B that emits blue light, and the like between the substrate 351 and the substrate 352.

[0503] Embodiment 3 can be referred to for the details of the light-emitting devices 130R, 130G, and 130B.

[0504] The light-emitting device 130R includes a conductive layer 224R, the conductive layer 151R over the conductive layer 224R, and the conductive layer 152R over the conductive layer 151R. The light-emitting device 130G includes a conductive layer 224G, the conductive layer 151G over the conductive layer 224G, and the conductive layer 152G over the conductive layer 151G. The light-emitting device 130B includes a conductive layer 224B, the conductive layer 151B over the conductive layer 224B, and the conductive layer 152B over the conductive layer 151B.

[0505] The conductive layer 224R is connected to a conductive layer 222b included in the transistor 205 through an opening provided in an insulating layer 214. An end portion of the conductive layer 151R is positioned outward from an end portion of the conductive layer 224R.

The insulating layer **156R** is provided to include a region that is in contact with the side surface of the conductive layer **151R**, and the conductive layer **152R** is provided to cover the conductive layer **151R** and the insulating layer **156R**.

[0506] The conductive layers **224G**, **151G**, and **152G** and the insulating layer **156G** in the light-emitting device **130G** are not described in detail because they are respectively similar to the conductive layers **224R**, **151R**, and **152R** and the insulating layer **156R** in the light-emitting device **130R**; the same applies to the conductive layers **224B**, **151B**, and **152B** and the insulating layer **156B** in the light-emitting device **130B**.

[0507] The conductive layers **224R**, **224G**, and **224B** each have a depressed portion covering the opening provided in the insulating layer **214**. A layer **128** is embedded in the depressed portion.

[0508] The layer **128** has a function of filling the depressed portions of the conductive layers **224R**, **224G**, and **224B** to obtain planarity. Over the conductive layers **224R**, **224G**, and **224B** and the layer **128**, the conductive layers **151R**, **151G**, and **151B** that are respectively electrically connected to the conductive layers **224R**, **224G**, and **224B** are provided. Thus, the regions overlapping with the depressed portions of the conductive layers **224R**, **224G**, and **224B** can also be used as light-emitting regions, whereby the aperture ratio of the pixel can be increased.

[0509] The layer **128** may be an insulating layer or a conductive layer. Any of a variety of inorganic insulating materials, organic insulating materials, and conductive materials can be used for the layer **128** as appropriate. Specifically, the layer **128** is preferably formed using an insulating material and is particularly preferably formed using an organic insulating material. The layer **128** can be formed using an organic insulating material usable for the insulating layer **127**, for example.

[0510] The protective layer **131** is provided over the light-emitting devices **130R**, **130G**, and **130B**. The protective layer **131** and the substrate **352** are bonded to each other with an adhesive layer **142**. The substrate **352** is provided with a light-blocking layer **157**. A solid sealing structure, a hollow sealing structure, or the like can be employed to seal the light-emitting device **130**. In FIG. **14**, a solid sealing structure is employed, in which a space between the substrate **352** and the substrate **351** is filled with the adhesive layer **142**. Alternatively, the space may be filled with an inert gas (e.g., nitrogen or argon), i.e., a hollow sealing structure may be employed. In that case, the adhesive layer **142** may be provided not to overlap with the light-emitting device. Alternatively, the space may be filled with a resin other than the frame-shaped adhesive layer **142**.

[0511] FIG. **14** illustrates an example where the connection portion **140** includes a conductive layer **224C** obtained by processing the same conductive film as the conductive layers **224R**, **224G**, and **224B**; the conductive layer **151C** obtained by processing the same conductive film as the conductive layers **151R**, **151G**, and **151B**; and the conductive layer **152C** obtained by processing the same conductive film as the conductive layers **152R**, **152G**, and **152B**. In the example illustrated in FIG. **14**, the insulating layer **156C** is provided to include a region overlapping with the side surface of the conductive layer **151C**.

[0512] The display device **100C** has a top-emission structure. Light from the light-emitting device is emitted toward the substrate **352**. For the substrate **352**, a material with a high visible-light-transmitting property is preferably used. The pixel electrode includes a material that reflects visible light, and the counter electrode (the common electrode **155**) includes a material that transmits visible light.

[0513] An insulating layer **211**, an insulating layer **213**, an insulating layer **215**, and the insulating layer **214** are provided in this order over the substrate **351**. Part of the insulating layer **211** functions as a gate insulating layer of each transistor. Part of the insulating layer **213** functions as a gate insulating layer of each transistor. The insulating layer **215** is provided to cover the transistors. The insulating layer **214** is provided to cover the transistors and has a function of a planarization layer. Note that the number of gate insulating layers and the number of insulating layers covering the transistors are not limited and may each be one or more.

[0514] An inorganic insulating film is preferably used as each of the insulating layers **211**, **213**, and

215.

[0515] An organic insulating layer is suitable as the insulating layer **214** functioning as a planarization layer.

[0516] Each of the transistors **201** and **205** includes a conductive layer **221** functioning as a gate, the insulating layer **211** functioning as the gate insulating layer, a conductive layer **222a** and the conductive layer **222b** functioning as a source and a drain, a semiconductor layer **231**, the insulating layer **213** functioning as the gate insulating layer, and a conductive layer **223** functioning as a gate.

[0517] A connection portion **204** is provided in a region of the substrate **351** not overlapping with the substrate **352**. In the connection portion **204**, one of the source electrode and the drain electrode of the transistor **201** is electrically connected to the FPC **353** through a conductive layer **166** and a connection layer **242**. An example is described in which the conductive layer **166** has a stacked-layer structure of a conductive film obtained by processing the same conductive film as the conductive layers **224R**, **224G**, and **224B**; a conductive film obtained by processing the same conductive film as the conductive layers **151R**, **151G**, and **151B**; and a conductive film obtained by processing the same conductive film as the conductive layers **152R**, **152G**, and **152B**. On the top surface of the connection portion **204**, the conductive layer **166** is exposed. Thus, the connection portion **204** and the FPC **353** can be electrically connected to each other through the connection layer **242**.

[0518] The light-blocking layer **157** is preferably provided on the surface of the substrate **352** on the substrate **351** side. The light-blocking layer **157** can be provided over a region between adjacent light-emitting devices, in the connection portion **140**, in the circuit **356**, and the like. A variety of optical members can be arranged on the outer surface of the substrate **352**.

[0519] A material that can be used for the substrate **120** can be used for each of the substrates **351** and **352**.

[0520] A material that can be used for the resin layer **122** can be used for the adhesive layer **142**.

[0521] As the connection layer **242**, an anisotropic conductive film (ACF), an anisotropic conductive paste (ACP), or the like can be used.

[Display Device **100D**]

[0522] The display device **100D** illustrated in FIG. **15** differs from the display device **100C** illustrated in FIG. **14** mainly in having a bottom-emission structure.

[0523] Light from the light-emitting device is emitted toward the substrate **351**. For the substrate **351**, a material with a high visible-light-transmitting property is preferably used. By contrast, there is no limitation on the light-transmitting property of a material used for the substrate **352**.

[0524] A light-blocking layer **317** is preferably formed between the substrate **351** and the transistor **201** and between the substrate **351** and the transistor **205**. FIG. **15** illustrates an example where the light-blocking layer **317** is provided over the substrate **351**, an insulating layer **153** is provided over the light-blocking layer **317**, and the transistors **201** and **205** and the like are provided over the insulating layer **153**.

[0525] The light-emitting device **130R** includes a conductive layer **112R**, a conductive layer **126R** over the conductive layer **112R**, and a conductive layer **129R** over the conductive layer **126R**.

[0526] The light-emitting device **130B** includes a conductive layer **112B**, a conductive layer **126B** over the conductive layer **112B**, and a conductive layer **129B** over the conductive layer **126B**.

[0527] A material with a high visible-light-transmitting property is used for each of the conductive layers **112R**, **112B**, **126R**, **126B**, **129R**, and **129B**. A material that reflects visible light is preferably used for the second electrode **102**.

[0528] Although not illustrated in FIG. **15**, the light-emitting device **130G** is also provided.

[0529] Although FIG. **15** and the like illustrate an example where the top surface of the layer **128** includes a flat portion, the shape of the layer **128** is not particularly limited.

[Display Device **100D2**]

[0530] The display device **100D2** illustrated in FIG. **16A** is an example of a bottom-emission display device different from the display device **100D** illustrated in FIG. **15**. The display device **100D2** is different from the display device **100D** in including an organic resin layer **180**. Note that in the drawings, reference numerals of some of the components that are shown in FIG. **15** are omitted; for the details of the components, the description made with reference to FIG. **15** is to be referred to.

[0531] FIG. **16B** shows a top-view layout of the pixels **178** (pixels **178a** and **178b**) each including the subpixels **110** (the subpixels **110R**, **110G**, and **110B** and a subpixel **110W**), and FIG. **16C** shows a top view of the organic resin layer **180** in a region where the subpixels **110R** and **110W** of the pixel **178** are formed. Note that the width between the light-blocking layer **317** and another light-blocking layer **317** corresponds to a width **110Rw** in the light-emitting region of the subpixel **110R**.

[0532] As illustrated in FIG. **16A**, the organic resin layer **180** is provided over the insulating layer **214**. As illustrated in FIG. **16C** and the region surrounded by the dashed-dotted line in FIG. **16A**, the organic resin layer **180** includes a depressed portion **181** (depressed portions **181a** and **181b**) having a curved surface at least in a region where the subpixel is formed. Note that the depressed portion **181** outside the light-emitting region, like a depressed portion **181c**, may also be provided. With the depressed portion **181c**, light emission caused in a region overlapping with the light-blocking layer **317** or light travelled into the region overlapping with the light-blocking layer **317** can be refracted and extracted from the light-emitting region, whereby emission efficiency can be improved.

[0533] A plurality of the depressed portions **181** may be formed in a matrix. The depressed portions **181a** and **181b** may be provided in contact with each other or may be provided to have a flat surface therebetween.

[0534] Although the top-view shape and the cross-sectional shape of the depressed portion are hexagonal (FIG. **16C**) and semicircular (FIG. **16A**), respectively, other shapes may be employed as needed. Examples of the top-view shape of the depressed portion include polygons such as a triangle, a tetragon (including a rectangle and a square), and a pentagon; these polygons with rounded corners; an ellipse; and a circle.

[0535] An insulating layer including an organic material can be used as the organic resin layer **180**. Examples of materials that can be used for the organic resin layer **180** include an acrylic resin, a polyimide resin, an epoxy resin, an imide resin, a polyamide resin, a polyimide-amide resin, a silicone resin, a siloxane resin, a benzocyclobutene-based resin, a phenol resin, and precursors of these resins. The organic resin layer **180** may be formed using an organic material such as polyvinyl alcohol (PVA), polyvinyl butyral, polyvinylpyrrolidone, polyethylene glycol, polyglycerin, pullulan, water-soluble cellulose, or an alcohol-soluble polyamide resin.

[0536] A photosensitive resin can also be used for the organic resin layer **180**. A photoresist may be used as the photosensitive resin. As the photosensitive resin, a positive photosensitive material or a negative photosensitive material can be used.

[0537] The organic resin layer **180** may include a material absorbing visible light. For example, the organic resin layer **180** itself may be made of a material absorbing visible light, or the organic resin layer **180** may include a pigment absorbing visible light. For example, the organic resin layer **180** can be formed using a resin that can be used as a color filter transmitting red, blue, or green light and absorbing light of the other colors or a resin that contains carbon black as a pigment and functions as a black matrix.

[0538] The first electrodes **101** (the first electrode **101R** and a first electrode **101W**) are over the organic resin layer **180**, and the organic compound layer **103** is over the first electrodes **101**. End portions of the first electrode **101** and the organic compound layer **103** may be covered with the insulating layer **127**.

[0539] Along the depressed portion of the organic resin layer **180**, the first electrode **101** formed over the organic resin layer **180** has a depressed portion in a manner similar to that of the organic

resin layer **180**. Furthermore, along the depressed portion of the first electrode **101**, the organic compound layer **103** formed over the first electrode **101** has a depressed portion in a manner similar to that of the first electrode **101**. Furthermore, along the depressed portion of the organic compound layer **103**, the common layer **104** formed over the organic compound layer **103** has a depressed portion in a manner similar to that of the organic compound layer **103**. Furthermore, along the depressed portion of the common layer **104**, the second electrode **102** formed over the common layer **104** has a depressed portion in a manner similar to that of the common layer **104**. That is, the depressed portions of the organic resin layer **180**, the first electrode **101**, the organic compound layer **103**, the common layer **104**, and the second electrode **102** overlap with each other. [0540] The common layer **104** is provided over the organic compound layer **103** and the insulating layer **127**, and the second electrode **102** is provided over the common layer **104**. The protective layer **131** is provided over the second electrode **102**, and the substrate **352** is bonded with the use of the adhesive layer **142**.

[0541] Although the light-emitting devices **130G** and **130B** are not illustrated in FIGS. **16A** to **16C**, the light-emitting devices **130G** and **130B** are also provided.

[Display Device **100E**]

[0542] The display device **100E** illustrated in FIG. **17** is a variation example of the display device **100C** illustrated in FIG. **14** and differs from the display device **100C** mainly in including the coloring layers **132R**, **132G**, and **132B**.

[0543] In the display device **100E**, the light-emitting device **130** includes a region overlapping with one of the coloring layers **132R**, **132G**, and **132B**. The coloring layers **132R**, **132G**, and **132B** can be provided on a surface of the substrate **352** on the substrate **351** side. End portions of the coloring layers **132R**, **132G**, and **132B** can overlap with the light-blocking layer **157**.

[0544] In the display device **100E**, the light-emitting device **130** can emit white light, for example. The coloring layer **132R**, the coloring layer **132G**, and the coloring layer **132B** can transmit red light, green light, and blue light, respectively, for example. Note that in the display device **100E**, the coloring layers **132R**, **132G**, and **132B** may be provided between the protective layer **131** and the adhesive layer **142**.

[Display Device **100E2**]

[0545] The display device **100E2** illustrated in FIG. **18A** is a variation example of the display device **100E** illustrated in FIG. **17** and includes microlenses **182** over the coloring layers **132R**, **132G**, and **132B**. Note that in the drawings, reference numerals of some of the components that are shown in FIG. **17** are omitted; for the details of the components, the description made with reference to FIG. **17** is to be referred to.

[0546] FIG. **18B** shows a top-view layout of the pixels **178** (the pixels **178a** and **178b**) each including the subpixels **110** (the subpixels **110R**, **110G**, and **110B**), and FIG. **18C** shows a top view of the microlenses **182** in a region where the subpixels **110R**, **110G**, and **110B** of the pixels **178** are formed. Note that the width of the region where the common electrode **155** and the organic compound layer **103** are in contact with each other corresponds to a width **110Gw** in the light-emitting region of the subpixel **110G**.

[0547] In the display device **100E2** illustrated in FIG. **18A**, a planarization film **143** is provided over the protective layer **131**, and the coloring layers **132R**, **132G**, and **132B** are provided over the planarization film **143**. A planarization film **144** is provided to cover the coloring layers **132R**, **132G**, and **132B**. The microlenses **182** are provided over the planarization film **144**.

[0548] Note that as illustrated in FIG. **18C**, the microlens **182** is preferably provided for each of the subpixels in the region where the subpixels are formed.

[0549] Although the top-view shape of the microlens **182** is hexagonal in FIG. **18C**, a different shape may be employed as needed. Examples of the top-view shape of the microlens **182** include polygons such as a triangle, a tetragon (including a rectangle and a square), and a pentagon; these polygons with rounded corners; an ellipse; and a circle.

[0550] The microlenses **182** can be formed using a material similar to that for the organic resin layer **180**.

[0551] This embodiment can be combined as appropriate with the other embodiments or the examples. In this specification, in the case where a plurality of structure examples are shown in one embodiment, the structure examples can be combined as appropriate.

Embodiment 5

[0552] In this embodiment, electronic appliances of embodiments of the present invention will be described.

[0553] Electronic appliances in this embodiment each include the display device of one embodiment of the present invention in a display portion. The display device of one embodiment of the present invention has low power consumption and high reliability. Thus, the display device of one embodiment of the present invention can be used for display portions of a variety of electronic appliances.

[0554] Examples of the electronic appliances include a digital camera, a digital video camera, a digital photo frame, a mobile phone, a portable game console, a portable information terminal, and an audio reproducing device, in addition to electronic appliances with a relatively large screen, such as a television device, desktop and notebook personal computers, a monitor of a computer and the like, digital signage, and a large game machine such as a pachinko machine.

[0555] Examples of wearable devices capable of being worn on a head are described with reference to FIGS. **19A** to **19D**.

[0556] An electronic appliance **700A** illustrated in FIG. **19A** and an electronic appliance **700B** illustrated in FIG. **19B** each include a pair of display panels **751**, a pair of housings **721**, a communication portion (not illustrated), a pair of wearing portions **723**, a control portion (not illustrated), an image capturing portion (not illustrated), a pair of optical members **753**, a frame **757**, and a pair of nose pads **758**.

[0557] The display device of one embodiment of the present invention can be used for the display panels **751**. Thus, a highly reliable electronic appliance is obtained.

[0558] The electronic appliances **700A** and **700B** can each project images displayed on the display panels **751** onto display regions **756** of the optical members **753**. Since the optical members **753** have a light-transmitting property, the user can see images displayed on the display regions, which are superimposed on transmission images seen through the optical members **753**.

[0559] In the electronic appliances **700A** and **700B**, a camera capable of capturing images of the front side may be provided as the image capturing portion. Furthermore, when the electronic appliances **700A** and **700B** are provided with an acceleration sensor such as a gyroscope sensor, the orientation of the user's head can be sensed and an image corresponding to the orientation can be displayed on the display regions **756**.

[0560] The communication portion includes a wireless communication device, and a video signal, for example, can be supplied by the wireless communication device. Instead of or in addition to the wireless communication device, a connector that can be connected to a cable for supplying a video signal and a power supply potential may be provided.

[0561] The electronic appliances **700A** and **700B** are provided with a battery, so that they can be charged wirelessly and/or by wire.

[0562] A touch sensor module may be provided in the housing **721**.

[0563] Various touch sensors can be applied to the touch sensor module. For example, any of touch sensors of the following types can be used: a capacitive type, a resistive type, an infrared type, an electromagnetic induction type, a surface acoustic wave type, and an optical type. In particular, a capacitive sensor or an optical sensor is preferably used for the touch sensor module.

[0564] An electronic appliance **800A** illustrated in FIG. **19C** and an electronic appliance **800B** illustrated in FIG. **19D** each include a pair of display portions **820**, a housing **821**, a communication portion **822**, a pair of wearing portions **823**, a control portion **824**, a pair of image capturing

portions **825**, and a pair of lenses **832**.

[0565] The display device of one embodiment of the present invention can be used in the display portions **820**. Thus, a highly reliable electronic appliance is obtained.

[0566] The display portions **820** are positioned inside the housing **821** so as to be seen through the lenses **832**. When the pair of display portions **820** display different images, three-dimensional display using parallax can be performed.

[0567] The electronic appliances **800A** and **800B** preferably include a mechanism for adjusting the lateral positions of the lenses **832** and the display portions **820** so that the lenses **832** and the display portions **820** are positioned optimally in accordance with the positions of the user's eyes.

[0568] The electronic appliance **800A** or the electronic appliance **800B** can be mounted on the user's head with the wearing portions **823**.

[0569] The image capturing portion **825** has a function of obtaining information on the external environment. Data obtained by the image capturing portion **825** can be output to the display portion **820**. An image sensor can be used for the image capturing portion **825**. Moreover, a plurality of cameras may be provided so as to support a plurality of fields of view, such as a telescope field of view and a wide field of view.

[0570] The electronic appliance **800A** may include a vibration mechanism that functions as bone-conduction earphones.

[0571] The electronic appliances **800A** and **800B** may each include an input terminal. To the input terminal, a cable for supplying a video signal from a video output device or the like, power for charging a battery provided in the electronic appliance, and the like can be connected.

[0572] The electronic appliance of one embodiment of the present invention may have a function of performing wireless communication with earphones **750**.

[0573] The electronic appliance may include an earphone portion. The electronic appliance **700B** illustrated in FIG. **19B** includes earphone portions **727**. Part of a wiring that connects the earphone portion **727** and the control portion may be positioned inside the housing **721** or the wearing portion **723**.

[0574] Similarly, the electronic appliance **800B** illustrated in FIG. **19D** includes earphone portions **827**. For example, the earphone portion **827** can be connected to the control portion **824** by wire.

[0575] As described above, both the glasses-type device (e.g., the electronic appliances **700A** and **700B**) and the goggles-type device (e.g., the electronic appliances **800A** and **800B**) are preferable as the electronic appliance of one embodiment of the present invention.

[0576] An electronic appliance **6500** illustrated in FIG. **20A** is a portable information terminal that can be used as a smartphone.

[0577] The electronic appliance **6500** includes a housing **6501**, a display portion **6502**, a power button **6503**, buttons **6504**, a speaker **6505**, a microphone **6506**, a camera **6507**, a light source **6508**, and the like. The display portion **6502** has a touch panel function.

[0578] The display device of one embodiment of the present invention can be used in the display portion **6502**. Thus, a highly reliable electronic appliance is obtained.

[0579] FIG. **20B** is a schematic cross-sectional view including an end portion of the housing **6501** on the microphone **6506** side.

[0580] A protection member **6510** having a light-transmitting property is provided on the display surface side of the housing **6501**. A display panel **6511**, an optical member **6512**, a touch sensor panel **6513**, a printed circuit board **6517**, a battery **6518**, and the like are provided in a space surrounded by the housing **6501** and the protection member **6510**.

[0581] The display panel **6511**, the optical member **6512**, and the touch sensor panel **6513** are fixed to the protection member **6510** with a bonding layer (not illustrated).

[0582] Part of the display panel **6511** is folded back in a region outside the display portion **6502**, and an FPC **6515** is connected to the part that is folded back. An IC **6516** is mounted on the FPC **6515**. The FPC **6515** is connected to a terminal provided on the printed circuit board **6517**.

[0583] The display device of one embodiment of the present invention can be used in the display panel **6511**. Thus, an extremely lightweight electronic appliance can be achieved. Since the display panel **6511** is extremely thin, the battery **6518** with high capacity can be mounted without an increase in the thickness of the electronic appliance. Moreover, part of the display panel **6511** is folded back so that a connection portion with the FPC **6515** is provided on the back side of the pixel portion, whereby an electronic appliance with a narrow bezel can be achieved.

[0584] FIG. **20C** illustrates an example of a television device. In a television device **7100**, a display portion **7000** is incorporated in a housing **7171**. Here, the housing **7171** is supported by a stand **7173**.

[0585] The display device of one embodiment of the present invention can be used in the display portion **7000**. Thus, a highly reliable electronic appliance is obtained.

[0586] Operation of the television device **7100** illustrated in FIG. **20C** can be performed with an operation switch provided in the housing **7171** and a separate remote control **7151**.

[0587] FIG. **20D** illustrates an example of a notebook personal computer. A notebook personal computer **7200** includes a housing **7211**, a keyboard **7212**, a pointing device **7213**, an external connection port **7214**, and the like. The display portion **7000** is incorporated in the housing **7211**.

[0588] The display device of one embodiment of the present invention can be used in the display portion **7000**. Thus, a highly reliable electronic appliance is obtained.

[0589] FIGS. **20E** and **20F** illustrate examples of digital signage.

[0590] Digital signage **7300** illustrated in FIG. **20E** includes a housing **7301**, the display portion **7000**, a speaker **7303**, and the like. The digital signage **7300** can also include an LED lamp, an operation key (including a power switch or an operation switch), a connection terminal, a variety of sensors, a microphone, and the like.

[0591] FIG. **20F** illustrates digital signage **7400** attached to a cylindrical pillar **7401**. The digital signage **7400** includes the display portion **7000** provided along a curved surface of the pillar **7401**.

[0592] In FIGS. **20E** and **20F**, the display device of one embodiment of the present invention can be used in the display portion **7000**. Thus, a highly reliable electronic appliance is obtained.

[0593] A larger area of the display portion **7000** can increase the amount of information that can be provided at a time. The larger display portion **7000** attracts more attention, so that the effectiveness of the advertisement can be increased, for example.

[0594] As illustrated in FIGS. **20E** and **20F**, it is preferable that the digital signage **7300** or the digital signage **7400** can work with an information terminal **7311** or an information terminal **7411**, such as a smartphone that a user has, through wireless communication.

[0595] Electronic appliances illustrated in FIGS. **21A** to **21G** include a housing **9000**, a display portion **9001**, a speaker **9003**, an operation key **9005** (including a power switch or an operation switch), a connection terminal **9006**, a sensor **9007** (a sensor having a function of measuring force, displacement, position, speed, acceleration, angular velocity, rotational frequency, distance, light, liquid, magnetism, temperature, chemical substance, sound, time, hardness, electric field, current, voltage, electric power, radiation, flow rate, humidity, gradient, oscillation, odor, or infrared rays), a microphone **9008**, and the like.

[0596] The electronic appliances illustrated in FIGS. **21A** to **21G** have a variety of functions. For example, the electronic appliances can have a function of displaying a variety of information (e.g., a still image, a moving image, and a text image) on the display portion, a touch panel function, a function of displaying a calendar, date, time, and the like, a function of controlling processing with use of a variety of software (programs), a wireless communication function, and a function of reading out and processing a program or data stored in a recording medium.

[0597] The electronic appliances illustrated in FIGS. **21A** to **21G** are described in detail below.

[0598] FIG. **21A** is a perspective view of a portable information terminal **9171**. The portable information terminal **9171** can be used as a smartphone, for example. The portable information terminal **9171** may include the speaker **9003**, the connection terminal **9006**, the sensor **9007**, or the

like. The portable information terminal **9171** can display text and image information on its plurality of surfaces. FIG. **21A** illustrates an example where three icons **9050** are displayed. Furthermore, information **9051** indicated by dashed rectangles can be displayed on another surface of the display portion **9001**. Examples of the information **9051** include notification of reception of an e-mail, an SNS message, an incoming call, or the like, the title and sender of an e-mail, an SNS message, or the like, the date, the time, remaining battery, and the radio field intensity. Alternatively, the icon **9050** or the like may be displayed at the position where the information **9051** is displayed.

[0599] FIG. **21B** is a perspective view of a portable information terminal **9172**. The portable information terminal **9172** has a function of displaying information on three or more surfaces of the display portion **9001**. In the example illustrated here, information **9052**, information **9053**, and information **9054** are displayed on different surfaces. For example, the user of the portable information terminal **9172** can check the information **9053** displayed such that it can be seen from above the portable information terminal **9172**, with the portable information terminal **9172** put in a breast pocket of his/her clothes.

[0600] FIG. **21C** is a perspective view of a tablet terminal **9173**. The tablet terminal **9173** is capable of executing a variety of applications such as mobile phone calls, e-mailing, viewing and editing texts, music reproduction, Internet communication, and a computer game, for example. The tablet terminal **9173** includes the display portion **9001**, the camera **9002**, the microphone **9008**, and the speaker **9003** on the front surface of the housing **9000**; the operation keys **9005** as buttons for operation on the left side surface of the housing **9000**; and the connection terminal **9006** on the bottom surface of the housing **9000**.

[0601] FIG. **21D** is a perspective view of a watch-type portable information terminal **9200**. The portable information terminal **9200** can be used as a Smartwatch (registered trademark), for example. The display surface of the display portion **9001** is curved, and an image can be displayed on the curved display surface. Furthermore, for example, mutual communication between the portable information terminal **9200** and a headset capable of wireless communication can be performed, and thus hands-free calling is possible. With the connection terminal **9006**, the portable information terminal **9200** can perform mutual data transmission with another information terminal and charging. Note that the charging operation may be performed by wireless power feeding.

[0602] FIGS. **21E** to **21G** are perspective views of a foldable portable information terminal **9201**. FIG. **21E** is a perspective view illustrating the portable information terminal **9201** that is opened. FIG. **21G** is a perspective view illustrating the portable information terminal **9201** that is folded. FIG. **21F** is a perspective view illustrating the portable information terminal **9201** that is shifted from one of the states in FIGS. **21E** and **21G** to the other. The portable information terminal **9201** is highly portable when folded. When the portable information terminal **9201** is opened, a seamless large display region is highly browsable. The display portion **9001** of the portable information terminal **9201** is supported by three housings **9000** joined together by hinges **9055**. The display portion **9001** can be folded with a radius of curvature greater than or equal to 0.1 mm and less than or equal to 150 mm, for example.

[0603] This embodiment can be combined as appropriate with the other embodiments or the examples. In this specification, in the case where a plurality of structure examples are shown in one embodiment, the structure examples can be combined as appropriate.

Example 1

[0604] Specific fabrication methods and characteristics of a light-emitting device **R1**, a light-emitting device **G1**, and a light-emitting device **B1**, which are light-emitting devices of one embodiment of the present invention, and a comparative light-emitting device **R1**, a comparative light-emitting device **G1**, and a comparative light-emitting device **B1**, which are comparative light-emitting devices, are described in this example. Structural formulae of main compounds used in this example are shown below.

##STR00013## ##STR00014## ##STR00015## ##STR00016##

(Fabrication Method of Light-Emitting Device R1)

[0605] First, 100-nm-thick silver (Ag) and 85-nm-thick indium tin oxide containing silicon oxide (ITSO) were stacked over a glass substrate sequentially from the substrate side by a sputtering method as a reflective electrode and a transparent electrode, respectively, whereby the first electrode **101** with a size of 2 mm×2 mm was formed. Note that the transparent electrode functions as an anode, and the transparent electrode and the reflective electrode are collectively regarded as the first electrode **101**.

[0606] Next, in pretreatment for fabricating the light-emitting device over the substrate, the surface of the substrate was washed with water, and baking was performed at 200° C. for one hour.

[0607] After that, the substrate was transferred into a vacuum evaporation apparatus where the pressure was reduced to approximately 1×10^{-4} Pa, and was subjected to vacuum baking at 170° C. for 30 minutes in a heating chamber of the vacuum evaporation apparatus, and then the substrate was cooled down for approximately 30 minutes.

[0608] Next, the substrate was fixed to a holder provided in the vacuum evaporation apparatus such that the surface on which the first electrode **101** was formed faced downward. Then, N-(biphenyl-2-yl)-N-(9,9-dimethylfluoren-2-yl)-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: oFBiSF(2)) represented by Structural Formula (i) above and a fluorine-containing material having an electron-acceptor property with a molecular weight of 672 (OCHD-003) were deposited by co-evaporation over the first electrode **101** to a thickness of 10 nm such that the weight ratio of oFBiSF(2) to OCHD-003 was 1:0.03, whereby the hole-injection layer **111** was formed.

[0609] Over the hole-injection layer **111**, oFBiSF(2) was deposited by evaporation to a thickness of 150 nm, whereby the first hole-transport layer was formed.

[0610] Next, 11-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]phenanthro[9',10':4,5]furo[2,3-b]pyrazine (abbreviation: 11mDBtBPPnfpr) represented by Structural Formula (ii) above, N-(biphenyl-4-yl)-N-[4-(9-phenyl-9H-carbazol-3-yl)phenyl]-9,9-dimethyl-9H-fluoren-2-amine (abbreviation: PCBBiF) represented by Structural Formula (iii) above, and a red phosphorescent material OCPG-006 were deposited by co-evaporation over the first hole-transport layer to a thickness of 40 nm such that the weight ratio of 11mDBtBPPnfpr to PCBBiF to OCPG-006 was 0.7:0.3:0.05, whereby the first light-emitting layer was formed.

[0611] Next, 9-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-9'-phenyl-2,3'-bi-9H-carbazole (abbreviation: mPCCzPTzn-02) represented by Structural Formula (iv) above was deposited by evaporation to a thickness of 10 nm, whereby the first electron-transport layer was formed.

[0612] After the first electron-transport layer was formed, 2,2'-(1,3-phenylene)bis(9-phenyl-1,10-phenanthroline) (abbreviation: mPPhen2P) represented by Structural Formula (v) above as the second organic compound having a phenanthroline skeleton and lithium oxide (Li.sub.2O) were deposited by co-evaporation to a thickness of 5 nm such that the weight ratio of mPPhen2P to Li.sub.2O was 1:0.02, whereby the first layer was formed. Then, copper phthalocyanine (abbreviation: CuPc) represented by Structural Formula (vii) above was deposited by evaporation to a thickness of 2 nm, whereby the third layer was formed. Furthermore, oFBiSF(2) and OCHD-003 were deposited by co-evaporation to a thickness of 10 nm such that the weight ratio of oFBiSF(2) to OCHD-003 was 1:0.15, whereby the second layer was formed. Thus, the intermediate layer was formed.

[0613] Over the intermediate layer, oFBiSF(2) was deposited by evaporation to a thickness of 65 nm, whereby the second hole-transport layer was formed.

[0614] Over the second hole-transport layer, 11mDBtBPPnfpr, PCBBiF, and OCPG-006 were deposited by co-evaporation to a thickness of 40 nm such that the weight ratio of 11 mDBtBPPnfpr to PCBBiF to OCPG-006 was 0.7:0.3:0.05, whereby the second light-emitting layer was formed.

[0615] Then, 2-[3'-(9,9-dimethyl-9H-fluoren-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mFBPTzn) represented by Structural Formula (viii) above was deposited to a thickness of 10 nm, and then 2,2'-[1,2-naphthalendiyl]di(4,1-phenylene)]bis(4,6-diphenyl-1,3,5-

triazine) (abbreviation: TznP2N) represented by Structural Formula (ix) above and 8-hydroxyquinolino-lithium (abbreviation: Liq) represented by Structural Formula (x) above were deposited by co-evaporation to a thickness of 25 nm such that the weight ratio of TznP2N to Liq was 1:1, whereby the second electron-transport layer was formed.

[0616] Then, Liq was deposited by evaporation to a thickness of 1 nm and silver (Ag) and magnesium (Mg) were deposited by co-evaporation to a thickness of 15 nm such that the volume ratio of Ag to Mg was 1:0.1, whereby the second electrode **102** was formed. Over the second electrode **102**, a film of 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzothiophene) (abbreviation: DBT3P-II) represented by Structural Formula (xi) above was formed to a thickness of 70 nm as a cap layer to improve light extraction efficiency.

[0617] Next, the light-emitting device was sealed using a glass substrate in a glove box containing a nitrogen atmosphere so as not to be exposed to the air. Specifically, a UV curable sealing material was applied to surround the device, only the sealing material was irradiated with UV while the light-emitting device was not irradiated with the UV, and heat treatment was performed at 80° C. under an atmospheric pressure for one hour. In this manner, the light-emitting device R1 was fabricated.

(Fabrication Method of Comparative Light-Emitting Device R1)

[0618] The comparative light-emitting device R1 was fabricated in a manner similar to that of the light-emitting device R1 except that 4-[3,5-bis(9H-carbazol-9-yl)phenyl]-2-phenyl-6-(biphenyl-4-yl)pyrimidine (abbreviation: 6BP-4Cz2PPm) represented by Structural Formula (xii) above was used instead of TznP2N in the second electron-transport layer.

(Fabrication Method of Light-Emitting Device G1)

[0619] The light-emitting device G1 was fabricated in a manner similar to that of the light-emitting device R1 except that the thickness of the first hole-transport layer was changed to 80 nm, the thickness of the second hole-transport layer was changed to 50 nm, and the first light-emitting layer and the second light-emitting layer were each formed by co-evaporation of 8-(1,1':4',1''-terphenyl-3-yl-2,4,5,6,2',3',5',6',2'',3'',4'',5'',6''-d.sub.13)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm-d.sub.13) represented by Structural Formula (xiii) above, 9-(2-naphthyl)-9'-phenyl-3,3'-bi-9H-carbazole (abbreviation: β NCCP) represented by Structural Formula (xiv) above, and [2-d.sub.3-methyl-8-(2-pyridinyl-N)benzofuro[2,3-b]pyridine- κ C]bis[2-(5-d.sub.3-methyl-2-pyridinyl- κ N.sup.2)phenyl- κ C]iridium(III) (abbreviation: Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3)) represented by Structural Formula (xv) above such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP to Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) was 0.5:0.5:0.1. A combination of 8mpTP-4mDBtPBfpm-d.sub.13, which is an organic compound containing deuterium, and β NCCP forms an exciplex. Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) is an organometallic complex that emits phosphorescent light. The T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP were 2.55 eV and 2.55 eV, respectively, and the difference therebetween was 0.00 eV.

(Fabrication Method of Light-Emitting Device G2)

[0620] The light-emitting device G2 was fabricated in a manner similar to that of the light-emitting device G1 except that 8-(p-terphenyl-3-yl)-4-[3-(dibenzothiophen-4-yl)phenyl]-benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm) represented by Structural Formula (xvi) above was used instead of 8mpTP-4mDBtPBfpm-d.sub.13 and 9-(2-naphthyl-1,3,4,5,6,7,8-d.sub.7)-9'-(phenyl-2,3,4,5,6-d.sub.5)-3,3'-bi-9H-carbazole-1,1',2,2',4,4',5,5',6,6',7,7',8,8'-d.sub.14 (abbreviation: β NCCP-d.sub.26) represented by Structural Formula (xvii) above was used instead of β NCCP. A combination of β NCCP-d.sub.26, which is an organic compound containing deuterium, and 8mpTP-4mDBtPBfpm forms an exciplex in combination. The T.sub.1 levels of 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 were 2.55 eV and 2.56 eV, respectively, and the difference therebetween was 0.01 eV.

(Fabrication Method of Light-Emitting Device G3)

[0621] The light-emitting device G3 was fabricated in a manner similar to that of the light-emitting device G1 except that β NCCP-d.sub.26 was used instead of β NCCP. A combination of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 forms an exciplex. The T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 were 2.55 eV and 2.56 eV, respectively, and the difference therebetween was 0.01 eV.

(Fabrication Method of Comparative Light-Emitting Device G1)

[0622] The comparative light-emitting device G1 was fabricated in a manner similar to that of the light-emitting device G1 except that in the second electron-transport layer, 6BP-4Cz2PPm was used instead of TznP2N and 8mpTP-4mDBtPBfpm was used instead of 8mpTP-4mDBtPBfpm-d.sub.13.

(Fabrication Method of Light-Emitting Device B1)

[0623] The light-emitting device B1 was fabricated in a manner similar to that of the light-emitting device R1 except that the thickness of the first hole-transport layer was changed to 45 nm, the thickness of the second hole-transport layer was changed to 45 nm, and the first light-emitting layer and the second light-emitting layer were each formed to a thickness of 25 nm by co-evaporation of 9-(1-naphthyl)-10-[4-(2-naphthyl)phenyl]anthracene (abbreviation: α N-PNPAnth) represented by Structural Formula (xviii) above and N,N-diphenyl-N,N-bis(9-phenyl-9H-carbazol-2-yl)naphtho[2,3-b;6,7-b']bisbenzofuran-3,10-diamine (abbreviation: 3,10PCA2Nbf(IV)-02) represented by Structural Formula (xix) above such that the weight ratio of α N- β NPAnth to 3,10PCA2Nbf(IV)-02 was 1:0.015.

(Fabrication Method of Comparative Light-Emitting Device B1)

[0624] The comparative light-emitting device B1 was fabricated in a manner similar to that of the light-emitting device B1 except that 6BP-4Cz2PPm was used instead of TznP2N in the second electron-transport layer.

[0625] The structures of the light-emitting device R1, the light-emitting devices G1 to G3, the light-emitting device B1, the comparative light-emitting device R1, the comparative light-emitting device G1, and the comparative light-emitting device B1 are shown below.

TABLE-US-00001 TABLE 1 Comparative Thickness Light-emitting light-emitting (nm) device R1 device R1 Cap layer 70 DBT3P-II Second electrode 2 15 Ag:Mg (1:0.1) 1 1 Liq Second b 25 TznP2N:Liq 6BP-4Cz2PPm:Liq electron-transport layer (1:1) (1:1) a 10 mFBPTzn Second light-emitting layer 40 11mDBtBPPnfpr:PCBBiF:OCPG-006 (0.7:0.3:0.05) Second 65 oFBISF(2) hole-transport layer Intermediate Second layer 10 oFBiSF(2):OCHD-003 (1:0.15) layer Third layer 2 CuPc First layer 5 mPPhen2P:Li.sub.2O (1:0.02) First 10 mPCCzPTzn-02 electron-transport layer First light-emitting layer 40 11mDBtBPPnfpr:PCBBiF:OCPG-006 (0.7:0.3:0.05) First 150 oFBiSF(2) hole-transport layer Hole-injection layer 10 oFBiSF(2):OCHD-003 (1:0.03) First electrode 2 85 ITSO 1 100 Ag

TABLE-US-00002 TABLE 2 Light- Light- Light- Comparative emitting emitting emitting light-emitting Thickness device device device device (nm) G1 G2 G3 G1 Cap layer 70 DBT3P-II Second electrode 2 15 Ag:Mg (1:0.1) 1 1 Liq Second b 25 TznP2N:Liq 6BP-4Cz2PPm:Liq electron-transport layer (1:1) (1:1) a 10 mFBPTzn Second light-emitting layer 40 *1 Second 50 oFBiSF(2) hole-transport layer Intermediate Second layer 10 oFBiSF(2):OCHD-003 (1:0.15) layer Third layer 2 CuPc First layer 5 mPPhen2P:Li.sub.2O (1:0.02) First 10 mPCCzPTzn-02 electron-transport layer First light-emitting layer 40 *1 First 80 oFBiSF(2) hole-transport layer Hole-injection layer 10 oFBiSF(2):OCHD-003 (1:0.03) First electrode 2 85 ITSO 1 100 Ag

TABLE-US-00003 TABLE 3 *1 Light-emitting 8mpTP-4mDBtPBfpm-d.sub.13; β NCCP:Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) device G1 (0.5:0.5:0.1) Light-emitting 8mpTP-4mDBtPBfpm; β NCCP-d.sub.26:Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) device G2 (0.5:0.5:0.1) Light-emitting 8mpTP-4mDBtPBfpm-d.sub.13; β NCCP-d.sub.26:Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) device G3 (0.5:0.5:0.1) Comparative 8mp TP-4mDBtPBfpm; β NCCP:Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) light-emitting (0.5:0.5:0.1)

device G1

TABLE-US-00004 TABLE 4 Comparative Thickness Light-emitting light-emitting (nm) device B1 device B1 Cap layer 70 DBT3P-II Second electrode 2 15 Ag:Mg (1:0.1) 1 1 Liq Second b 25 TznP2N:Liq 6BP-4Cz2PPm:Liq electron-transport layer (1:1) (1:1) a 10 mFBPTzn Second light-emitting layer 25 α N- β NPAnth:3,10PCA2Nbf(IV)-02 (1:0.015) Second 45 oFBiSF(2) hole-transport layer Intermediate Second layer 10 oFBiSF(2):OCHD-003 (1:0.15) layer Third layer 2 CuPc First layer 5 mPPhen2P:Li.sub.2O (1:0.02) First 10 mPCCzPTzn-02 electron-transport layer First light-emitting layer 25 α N- β NPAnth:3,10PCA2Nbf(IV)-02 (1:0.015) First 45 oFBiSF(2) hole-transport layer Hole-injection layer 10 oFBiSF(2):OCHD-003 (1:0.03) First electrode 2 85 ITSO 1 100 Ag

[0626] FIG. 23, FIG. 24, FIG. 25, FIG. 26, and FIG. 27 respectively show the luminance-current density characteristics, current efficiency-luminance characteristics, current density-voltage characteristics, power efficiency-luminance characteristics, and electroluminescence spectra of the light-emitting device R1 and the comparative light-emitting device R1. FIG. 28, FIG. 29, FIG. 30, FIG. 31, and FIG. 32 respectively show the luminance-current density characteristics, current efficiency-luminance characteristics, current density-voltage characteristics, power efficiency-luminance characteristics, and electroluminescence spectra of the light-emitting devices G1 to G3 and the comparative light-emitting device G1. FIG. 33, FIG. 34, FIG. 35, FIG. 36, FIG. 37, and FIG. 38 respectively show the luminance-current density characteristics, current efficiency-luminance characteristics, current density-voltage characteristics, power efficiency-luminance characteristics, blue index-luminance characteristics, and electroluminescence spectra of the light-emitting device B1 and the comparative light-emitting device B1.

[0627] Table 5 shows the main characteristics of the light-emitting device R1 and the comparative light-emitting device R1 at approximately 1000 cd/m.^{sup.2}. Table 6 shows those of the light-emitting devices G1 to G3 at approximately 1000 cd/m.^{sup.2}. Table 7 shows those of the light-emitting device B1 and the comparative light-emitting device B1 at approximately 1000 cd/m.^{sup.2}. The luminance, CIE chromaticity, and electroluminescence spectra were measured at room temperature with a spectroradiometer (SR-UL1R, TOPCON TECHNOHOUSE CORPORATION).

TABLE-US-00005 TABLE 5 Current Current Power Voltage Current density Chromaticity Chromaticity efficiency efficiency (V) (mA) (mA/cm.^{sup.2}) x y (cd/A) (lm/W) Light-emitting 5.20 0.06 1.4 0.69 0.31 56.9 34.4 device R1 Comparative 5.40 0.06 1.5 0.69 0.31 56.3 32.7 light-emitting device R1

[0628] FIGS. 23 to 27 and Table 5 reveal that red light emission with an electroluminescence spectrum peak wavelength of approximately 625 nm can be obtained from both the light-emitting device R1 and the comparative light-emitting device R1. Although both the light-emitting device R1 and the comparative light-emitting device R1 have high current efficiency, FIG. 25 shows that the light-emitting device R1 has lower driving voltage and more favorable characteristics than the comparative light-emitting device R1. This indicates that the light-emitting device R1 of one embodiment of the present invention is a tandem light-emitting device with favorable characteristics.

TABLE-US-00006 TABLE 6 Current Current Power Voltage Current density Chromaticity Chromaticity efficiency efficiency (V) (mA) (mA/cm.^{sup.2}) x y (cd/A) (lm/W) Light-emitting 5.40 0.02 0.4 0.23 0.73 223.9 130.2 device G1 Light-emitting 5.40 0.02 0.4 0.21 0.74 202.7 117.9 device G2 Light-emitting 5.40 0.02 0.4 0.22 0.73 204.9 119.2 device G3 Comparative 5.60 0.02 0.5 0.23 0.73 224.1 125.7 light-emitting device G1

[0629] FIGS. 28 to 32 and Table 6 reveal that green light emission with an electroluminescence spectrum peak wavelength of approximately 527 nm can be obtained from all the light-emitting devices G1 to G3 and the comparative light-emitting device G1. Although all the light-emitting devices G1 to G3 and the comparative light-emitting device G1 have high current efficiency, the

light-emitting device G1 has higher current efficiency than the other light-emitting devices. The light-emitting devices G1 to G3 have lower driving voltage, lower power consumption, and more favorable characteristics than the comparative light-emitting device G1. This indicates that the light-emitting devices G1 to G3 of one embodiment of the present invention are tandem light-emitting device with favorable characteristics.

[0630] Here, 8mpTP-4mDBtPBfpm is a non-deuterated organic compound of 8mpTP-4mDBtPBfpm-d.sub.13, and β NCCP is a non-deuterated organic compound of β NCCP-d.sub.26.

[0631] FIG. 39 shows the measurement results of emission spectra of an evaporated film of 8mpTP-4mDBtPBfpm-d.sub.13, an evaporated film of β NCCP-d.sub.26, and a film (a mixed film) formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP-d.sub.26 was 1:1. As shown in the graph, the emission spectrum of the co-evaporated film is on a longer wavelength side than the emission spectra of the organic compounds, which indicates that 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 form an exciplex in combination. Note that a combination of 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 and a combination of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP also form exciplexes.

[0632] FIG. 40 shows an emission spectrum of a film (a mixed film) formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP-d.sub.26 was 1:1 (a PL spectrum of an exciplex) and an absorption spectrum and an emission spectrum (a PL spectrum) of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3), which is the emission center substance. As shown in FIG. 40, the emission edge (442 nm) on a shorter wavelength side of the PL spectrum of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 is positioned at a shorter wavelength than the absorption edge (526 nm) on a longer wavelength side of the absorption spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3). Since the PL spectrum of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 and the absorption edge of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) have such a positional relation, excitation energy can be efficiently transferred to Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) in the light-emitting device G3. Furthermore, the emission edges on a shorter wavelength side of the PL spectra of the exciplex formed by 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 and the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP have a similar positional relation; thus, excitation energy can be efficiently transferred to Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) also in the light-emitting devices G1 and G2.

[0633] Alternatively, the peak wavelength (500 nm) of the PL spectrum of the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 is shorter than the peak wavelength (528 nm) of the PL spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3). The difference between the peak wavelength of the PL spectrum of the exciplex and the peak wavelength of the PL spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) is less than or equal to 30 nm. Since the peak wavelengths of the PL spectra of the exciplex and Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) have such a relation, energy can be efficiently transferred. Note that the peak wavelengths of the PL spectra of the exciplex formed by 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 and the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP have a similar positional relation; thus, excitation energy can be efficiently transferred to Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) also in the light-emitting devices G1 and G2.

[0634] Alternatively, the difference between the peak wavelength (500 nm) of the PL spectrum of the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 and the wavelength (526 nm) of the absorption edge on a longer wavelength side of the absorption spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) is 26 nm, which is less than or equal to 30 nm. Since the peak wavelength of the PL spectrum of the exciplex and the wavelength of the absorption edge on a longer wavelength side of the absorption spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) have such a relation, energy can be efficiently transferred. Note that the peak wavelengths

of the PL spectra of the exciplex formed by 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 and the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP have a similar positional relation; thus, excitation energy can be efficiently transferred to Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) also in the light-emitting devices G1 and G2.

[0635] Note that the PL spectrum of the exciplex was measured using a film formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26. The PL spectrum or the absorption spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) was measured using a solution thereof in which chloroform was used as a solvent.

[0636] The absorption edge of the absorption spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a longer wavelength side of the longest-wavelength peak (or the longest-wavelength shoulder peak) of the absorption spectrum has the maximum absolute value. The emission edge on a shorter wavelength side of the PL spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the PL spectrum has the maximum absolute value. FIG. 41 shows an example of determining the absorption edge of the absorption spectrum of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3). In this manner, the absorption edge of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) can be determined to be at 526 nm.

[0637] The HOMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -5.60 eV; the HOMO level of β NCCP was -5.62 eV; the HOMO level of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property was -6.3 eV (reference value); the HOMO level of 8mpTP-4mDBtPBfpm was -6.2 eV (reference value); the LUMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -2.19 eV; the LUMO level of β NCCP was -2.21 eV; the LUMO level of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property was -3.01 eV; and the LUMO level of 8mpTP-4mDBtPBfpm was -3.01 eV.

[0638] Since the HOMO level of the organic compound having a hole-transport property is higher than or equal to the HOMO level of the organic compound having an electron-transport property and the LUMO level of the organic compound having a hole-transport property is higher than or equal to the LUMO level of the organic compound having an electron-transport property, it was found that each of the light-emitting devices G1 to G3 can efficiently form an exciplex.

[0639] The HOMO level and the LUMO level of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) were -5.32 eV and -2.39 eV, respectively. The energy difference between the HOMO level and the LUMO level of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP was 2.61 eV, which corresponds to the energy difference between the HOMO level (-5.62 eV) of β NCCP as the organic compound having a hole-transport property and the LUMO level (-3.01 eV) of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property. The energy difference between the HOMO level and the LUMO level of the exciplex of 8mpTP-4mDBtPBfpm and β NCCP-d.sub.26 was 2.59 eV, which corresponds to the energy difference between the HOMO level (-5.60 eV) of β NCCP-d.sub.26 as the organic compound having a hole-transport property and the LUMO level (-3.01 eV) of 8mpTP-4mDBtPBfpm as the organic compound having an electron-transport property. The energy difference between the HOMO level and the LUMO level of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 was 2.59 eV, which corresponds to the energy difference between the HOMO level (-5.60 eV) of β NCCP-d.sub.26 as the organic compound having a hole-transport property and the LUMO level (-3.01 eV) of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property. The energy difference (2.93 eV) between the HOMO level (-5.32 eV) and the LUMO level (-2.39 eV) corresponding to the band gap of Ir(5mppy-d.sub.3).sub.2(mbfppy-d.sub.3) was found to be larger than the energy difference between the HOMO level and the LUMO level of the exciplex.

[0640] The values of the HOMO level and the LUMO level were obtained through a cyclic voltammetry (CV) measurement. In the cyclic voltammetry (CV) measurement, the values (E) of the HOMO and LUMO levels were calculated on the basis of an oxidation peak potential (E.sub.pa) and a reduction peak potential (E.sub.pc), which were obtained by changing the potential of a working electrode with respect to a reference electrode. In the measurement, a HOMO level and a LUMO level were obtained by potential scanning in the positive direction and potential scanning in the negative direction, respectively. The scanning speed in the measurement was 0.1 V/s. Specifically, a standard oxidation-reduction potential (E.sub.o) ($=E_{\text{sub.pa}}+E_{\text{sub.pc}}/2$) was calculated from an oxidation peak potential (E.sub.pa) and a reduction peak potential (E.sub.pc), which were obtained by the cyclic voltammogram of a material. Then, the standard oxidation-reduction potential (E.sub.o) was subtracted from the potential energy (E.sub.x) of the reference electrode with respect to a vacuum level, whereby each of the values (E)($=E_{\text{sub.x}}-E_{\text{sub.o}}$) of HOMO and LUMO levels was obtained. Note that the reversible oxidation-reduction wave was obtained in the above case; in the case where an irreversible oxidation-reduction wave is obtained, the HOMO level is calculated as follows: a value obtained by subtracting a predetermined value (0.1 eV) from an oxidation peak potential (E.sub.pa) is assumed to be a reduction peak potential (E.sub.pc), and a standard oxidation-reduction potential (E.sub.o) is calculated to one decimal place. To calculate the LUMO level, a value obtained by adding a predetermined value (0.1 eV) to a reduction peak potential (E.sub.pc) was assumed to be an oxidation peak potential (E.sub.pa), and a standard oxidation-reduction potential (E.sub.o) was calculated to one decimal place.

[0641] The T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13, 8mpTP-4mDBtPBfpm, β NCCP-d.sub.26, and β NCCP were measured. For calculation of the T.sub.1 level, a PL spectrum (a phosphorescent spectrum) was measured at a measurement temperature of 10 K using a 50-nm-thick thin film of a sample formed over a quartz substrate. The measurement was performed with a PL microscope (LabRAM HR-PL, produced by HORIBA, Ltd.) and a He—Cd laser (325 nm) as excitation light. Note that the emission edge was determined as the intersection between a tangent and the horizontal axis (representing wavelength) or the baseline, as shown in FIGS. 43 to 46. The tangent was drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the emission spectrum (phosphorescent spectrum) has the maximum absolute value. The T.sub.1 levels of the organic compounds are described below. As a result of the measurement, the T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13, 8mpTP-4mDBtPBfpm, β NCCP-d.sub.26, and β NCCP were 2.55 eV, 2.55 eV, 2.56 eV, and 2.55 eV, respectively. In each of the light-emitting devices G1 to G3, in which one or both of the first host material and the second host material are deuterated, the difference in the T.sub.1 level between the first host material and the second host material is less than or equal to 0.2 eV as described above, and the efficiency of energy transfer from the triplet excited state is improved by the influence of deuterium; thus, deterioration of the first host material and the second host material can be inhibited.

[0642] The phosphorescence lifetimes of β NCCP, β NCCP-d.sub.26, 8mpTP-4mDBtPBfpm, and 8mpTP-4mDBtPBfpm-d.sub.13 and the rate of change in phosphorescence lifetime owing to deuteration are shown below. Note that the excitation wavelength of β NCCP and β NCCP-d.sub.26 was 330 nm and the measured wavelength was 515 nm. The excitation wavelength of 8mpTP-4mDBtPBfpm and 8mpTP-4mDBtPBfpm-d.sub.13 was 320 nm and the measured wavelength was 515 nm. The results show that the phosphorescence lifetime of 8mpTP-4mDBtPBfpm-d.sub.13 is 1.80 times, i.e., more than 1.50 times, the phosphorescence lifetime of 8mpTP-4mDBtPBfpm, and the phosphorescence lifetime of β NCCP-d.sub.26 is 3.18 times, i.e., more than 3.00 times, the phosphorescence lifetime of β NCCP.

TABLE-US-00007 TABLE 7 Phosphorescence Increasing rate lifetime (deuterated/ (seconds) non-deuterated) β NCCP 1.63 3.18 β NCCP-d.sub.26 5.18 8mpTP-4mDBtPBfpm 2.98 1.80 8mpTP-

[0643] As shown in FIG. 22, the time at which the light amount becomes 50% of that at the start of the measurement was set as $t=0$, and the time taken for the light amount to attenuate to $1/e$ of that at $t=0$ was regarded as the phosphorescence lifetime. In the graphs in FIG. 22, the time at which the intensity reaches 50% of that at the start of the measurement is set as time 0 s, the light amount at 0 s is regarded as 1, and the time taken for the light amount to become $1/e$ is the phosphorescence lifetime.

[0644] The measurement was performed at liquid nitrogen temperature (77 K) with FP-8600 produced by JASCO Corporation, in which a liquid nitrogen cooling unit PMU-830 was set. A solution of a material was prepared in a glove box of LABstarM13 (1250/780) produced by MBRAUN in the following manner: a sample was dissolved in 2-MeTHF that had been subjected to freeze-pump-thaw, and the concentration of the solution was adjusted to approximately 1.2×10^{-4} M.

[0645] The prepared solution was put in a liquid sample cell (sample tube) LPH-140 for cooling produced by JASCO Corporation, the sample cell was put in a sample cell holder, and the sample cell holder was capped with a fixing nut. After liquid nitrogen was injected into a dewer of the cooling unit of FP-8600, the sample cell was taken out from the glove box and then cooled in the dewer of the unit filled with the liquid nitrogen.

[0646] The time-resolved measurement was performed in the following manner: a sample cell was irradiated with excitation light for approximately 30 seconds and the emission intensity attenuating after the excitation light was blocked by a shutter was measured at 10 ms intervals. For use in the phosphorescence lifetime measurement, the wavelength including as little fluorescence as possible is preferably selected after comparison between an emission spectrum in the phosphorescence mode and an emission spectrum in the fluorescence mode. The excitation wavelength used for the measurement can be appropriately selected, and is preferably 330 nm. The band widths of excitation light and measured light are each approximately 10 nm. Since light emission ideally attenuates single-exponentially, the time taken for the emission intensity to attenuate to $1/e$ with reference to the time at which the light amount becomes 50% of that at the start of the measurement can be defined as the phosphorescence lifetime.

[0647] FIG. 42 shows the time-dependence of normalized luminance of the light-emitting devices G1 to G3 and the comparative light-emitting device G1 at a current density of 50 mA/cm².

[0648] FIG. 42 shows that the light-emitting devices G1 to G3 each have a smaller time dependence of normalized luminance than the comparative light-emitting device G1, and in particular, the light-emitting device G3 has the smallest time dependence of normalized luminance, resulting in its high reliability.

TABLE-US-00008

TABLE 8	Current	Current	Power	Voltage	Current density	Chromaticity
	efficiency	efficiency	BI	(V)	(mA)	(mA/cm ²) x y
	(cd/A)	(lm/W)	(cd/A/y)			
Light-emitting device B1	7.60	0.52	13.1	0.15	0.04	7.8 3.2 192.6
Comparative light-emitting device B1	8.20	0.51	12.8	0.15	0.04	
Light-emitting device B1	7.4	2.8	175.7			

[0649] FIGS. 33 to 38 and Table 7 reveal that blue light emission with an electroluminescence spectrum peak wavelength of 454 nm can be obtained from both the light-emitting device B1 and the comparative light-emitting device B1. Although both the light-emitting device B1 and the comparative light-emitting device B1 have high current efficiency, the light-emitting device B1 has lower power consumption and more favorable characteristics because its driving voltage is lower than that of the comparative light-emitting device B1. The light-emitting device B1 has a high blue index. This indicates that the light-emitting device B1 of one embodiment of the present invention is a tandem light-emitting device with favorable characteristics. In addition, the light-emitting device B1 has especially favorable characteristics at a practical luminance of and above 500 cd/cm².

[0650] Note that the blue index (BI) is a value obtained by dividing current efficiency (cd/A) by the

y value of CIE chromaticity (x, y), and is one of the indicators of characteristics of blue light emission. As the y chromaticity value of blue light emission becomes smaller, the color purity thereof tends to be higher. Blue light emission having a small y chromaticity value and high color purity enables expression of blue colors with a wide range of chromaticity in a display. Using blue light emission with high color purity reduces the luminance of blue light emission necessary for a display to express white, leading to lower power consumption of the display. Thus, BI, which is current efficiency based on a y chromaticity value as one of the indicators of color purity of blue, is suitably used as a means for showing efficiency of blue light emission in some cases. The light-emitting device with higher BI can be regarded as a blue-light-emitting device having higher efficiency for a display.

[0651] Here, the second electron-transport layers of the light-emitting device R1, the light-emitting devices G1 to G3, and the light-emitting device B1 include the same material (the first organic compound having a triazine skeleton). Thus, the light-emitting devices of different emission colors of one embodiment of the present invention can each have favorable characteristics even when the second electron-transport layers of the light-emitting devices are made of the same material.

[0652] Next, a display device of this example including the light-emitting device R1, the light-emitting device G1, and the light-emitting device B1 respectively in red, green, and blue subpixels; a display device of this example including the light-emitting device R1, the light-emitting device G2, and the light-emitting device B1 respectively in red, green, and blue subpixels; a display device of this example including the light-emitting device R1, the light-emitting device G3, and the light-emitting device B1 respectively in red, green, and blue subpixels; and a display device of the comparative example including the comparative light-emitting device R1, the comparative light-emitting device G1, and the comparative light-emitting device B1 respectively in red, green, and blue subpixels were assumed. The power consumption of their display portions (except for the power consumption of a driving transistor, a driving circuit, and the like) was tentatively calculated. Note that each of the light-emitting devices assumed to be used in the display devices is a tandem light-emitting device, and the same emission center substance is used in the plurality of light-emitting layers in each of the light-emitting devices. Thus, both of the display devices employ a side-by-side patterning method.

[0653] The conditions of the display devices assumed for the tentative calculation are as follows.

TABLE-US-00009	
TABLE 9	
Panel size	5 inches (16:9)
Panel area	68.9 cm. ²
Aperture ratio	30%
Red	10%
Green	10%
Blue	10%
Effective luminance	1000 cd/m. ²
in displaying white on the entire screen	
Circularly polarizing plate	Not used

[0654] First, in each of the display devices under the above-described conditions, the luminance (effective luminance) of the light-emitting devices of RGB to obtain 1000 cd/m.² emission of white light with CIE 1931 chromaticity coordinates (x, y)=(0.31, 0.33) when the display device is made to emit white light from the entire screen was calculated.

[0655] Next, the luminance (intrinsic luminance) required to obtain the calculated effective luminance of the light-emitting devices of RGB was calculated in consideration of the aperture ratios. The intrinsic luminance is the luminance at which each light-emitting device actually emits light in order to obtain the effective luminance of 1000 cd/m.² when the display device is made to emit white light with CIE 1931 chromaticity coordinates (x, y)=(0.31, 0.33) from the entire screen. Since the aperture ratio of the whole display device subjected to the tentative calculation is 30% and the aperture ratio per emission color is 10%, the intrinsic luminance is approximately ten times the effective luminance.

[0656] From the measurement results of the light-emitting devices described above and the intrinsic luminance, the current density and voltage for making each light-emitting device emit light at the intrinsic luminance can be obtained. In other words, in each of the display devices under the above-described conditions, the current density and voltage of each light-emitting device to obtain 1000 cd/m.² luminance emission of white light with CIE 1931 chromaticity coordinates

(x, y)=(0.31, 0.33) when the display device is made to emit white light from the entire screen can be obtained.

[0657] The power consumption is calculated by multiplying the amount of current by the voltage. The amount of current is calculated by multiplying the current density, the panel area, and the aperture ratio. The display devices subjected to the tentative calculation each have a diagonal size of 5 inches, an aspect ratio of 16:9, a panel area of 68.9 cm.sup.2, and an aperture ratio of the light-emitting device of each color of 10%, and the amount of current can be calculated by multiplying the current density calculated in the previous paragraph by these values. Furthermore, power consumption of the light-emitting device of each emission color can be calculated by multiplying the amount of current by the voltage obtained in the previous paragraph. By calculating and summing up the power consumptions of the light-emitting devices of RGB, the total power consumption of the display portion of the display device (except for the power consumption of the driving transistor, the driving circuit, and the like) can be obtained.

[0658] Table 10 shows the calculated power consumption of a display device of this example (a display device 1) assumed to use the light-emitting device R1, the light-emitting device G1, and the light-emitting device B1; Table 11 shows the calculated power consumption of a display device of this example (a display device 2) assumed to use the light-emitting device R1, the light-emitting device G2, and the light-emitting device B1; Table 12 shows the calculated power consumption of a display device of this example (a display device 3) assumed to use the light-emitting device R1, the light-emitting device G3, and the light-emitting device B1; and Table 13 shows the calculated power consumption of a display device of the comparative example (a comparative display device) assumed to use the comparative light-emitting device R1, the comparative light-emitting device G1, and the comparative light-emitting device B1.

TABLE-US-00010 TABLE 10 Display device 1 Effective Intrinsic Current Current Current Power Chromaticity Chromaticity luminance luminance efficiency density amount Voltage consumption x y (cd/m.sup.2) (cd/m.sup.2) (cd/A) (mA/cm.sup.2) (mA) (V) (mW) Red 0.69 0.31 244 2438 55.2 4.4 30.4 5.75 174.9 Green 0.23 0.73 704 7039 215.2 3.3 22.5 6.39 144.0 Blue 0.15 0.04 52 524 7.9 6.6 45.7 7.34 335.0 All white 0.31 0.33 1000 — 69.9 — 98.6 — 653.9

TABLE-US-00011 TABLE 11 Display device 2 Effective Intrinsic Current Current Current Power Chromaticity Chromaticity luminance luminance efficiency density amount Voltage consumption x y (cd/m.sup.2) (cd/m.sup.2) (cd/A) (mA/cm.sup.2) (mA) (V) (mW) Red 0.69 0.31 252 2524 55.1 4.6 31.6 5.77 182.1 Green 0.21 0.74 696 6956 195.3 3.6 24.5 6.38 156.6 Blue 0.15 0.04 52 520 7.9 6.6 45.3 7.33 332.5 All white 0.31 0.33 1000 — 67.9 — 101.4 — 671.2

TABLE-US-00012 TABLE 12 Display device 3 Effective Intrinsic Current Current Current Power Chromaticity Chromaticity luminance luminance efficiency density amount Voltage consumption x y (cd/m.sup.2) (cd/m.sup.2) (cd/A) (mA/cm.sup.2) (mA) (V) (mW) Red 0.69 0.31 248 2480 55.1 4.5 31.0 5.76 178.5 Green 0.22 0.74 700 6998 196.5 3.6 24.5 6.42 157.6 Blue 0.15 0.04 52 522 7.9 6.6 45.5 7.34 333.7 All white 0.31 0.33 1000 — 68.2 — 101.0 — 669.7

TABLE-US-00013 TABLE 13 Comparative display device Effective Intrinsic Current Current Current Power Chromaticity Chromaticity luminance luminance efficiency density amount Voltage consumption x y (cd/m.sup.2) (cd/m.sup.2) (cd/A) (mA/cm.sup.2) (mA) (V) (mW) Red 0.69 0.31 240 2403 54.8 4.4 30.2 6.08 183.8 Green 0.23 0.73 705 7053 217.4 3.2 22.4 6.83 152.8 Blue 0.15 0.04 54 545 7.5 7.2 50.0 7.85 392.3 All white 0.31 0.33 1000 — 67.2 — 102.6 — 729.0

[0659] Table 10 to Table 13 show that the display device of this example has higher current efficiency in emitting white light and lower driving voltage than the display device of the comparative example. Moreover, the power consumption of the display device of this example is lower than that of the display device of the comparative example.

[0660] Thus, the display device including the tandem light-emitting devices in each of which the light-emitting layer includes the first host material and the second host material one or both of which are deuterated and the emission center substance, the second electron-transport layer

includes the first organic compound having a triazine skeleton, the intermediate layer includes the mixed layer of the second organic compound having a phenanthroline skeleton and lithium or a lithium compound, and the difference in maximum peak wavelength between the emission spectra of light emitted from the light-emitting layers is less than or equal to 30 nm has favorable characteristics with low power consumption.

Example 2

[0661] Specific fabrication methods and characteristics of a light-emitting device **R4**, a light-emitting device **G4**, and a light-emitting device **B4**, which are light-emitting devices of one embodiment of the present invention are described in this example. Structural formulae of main compounds used in this example are shown below.

##STR00017## ##STR00018## ##STR00019##

(Fabrication Method of Light-Emitting Device **R4**)

[0662] First, 100-nm-thick silver (Ag) and 85-nm-thick indium tin oxide containing silicon oxide (ITSO) were stacked over a glass substrate sequentially from the substrate side by a sputtering method as a reflective electrode and a transparent electrode, respectively, whereby the first electrode **101** with a size of 2 mm×2 mm was formed. Note that the transparent electrode functions as an anode, and the transparent electrode and the reflective electrode are collectively regarded as the first electrode **101**.

[0663] Next, in pretreatment for fabricating the light-emitting device over the substrate, the surface of the substrate was washed with water, and baking was performed at 200° C. for one hour.

[0664] After that, the substrate was transferred into a vacuum evaporation apparatus where the pressure was reduced to approximately 1×10^{-4} Pa, and was subjected to vacuum baking at 170° C. for 30 minutes in a heating chamber of the vacuum evaporation apparatus, and then the substrate was cooled down for approximately 30 minutes.

[0665] Next, the substrate was fixed to a holder provided in the vacuum evaporation apparatus such that the surface on which the first electrode **101** was formed faced downward. Then, N-(biphenyl-2-yl)-N-(9,9-dimethylfluoren-2-yl)-9,9'-spirobi[9H-fluoren]-2-amine (abbreviation: oFBiSF(2)) represented by Structural Formula (i) above and a fluorine-containing material having an electron-acceptor property with a molecular weight of 672 (OCHD-003) were deposited by co-evaporation over the first electrode **101** to a thickness of 10 nm such that the weight ratio of oFBiSF(2) to OCHD-003 was 1:0.03, whereby the hole-injection layer **111** was formed.

[0666] Over the hole-injection layer **111**, oFBiSF(2) was deposited by evaporation to a thickness of 160 nm, whereby the first hole-transport layer was formed.

[0667] Next, 11-[3'-(dibenzothiophen-4-yl)biphenyl-3-yl]phenanthro[9',10':4,5]furo[2,3-b]pyrazine (abbreviation: 11mDBtBPPnfpr) represented by Structural Formula (ii) above, 9-(2-naphthyl-1,3,4,5,6,7,8-d.sub.7)-9'-(phenyl-2,3,4,5,6-d.sub.5)-3,3'-bi-9H-carbazole-1,1',2,2',4,4',5,5',6,6',7,7',8,8'-d.sub.4 (abbreviation: β NCCP-d.sub.26) represented by Structural Formula (xvii) above, and a red phosphorescent material OCPG-006 were deposited by co-evaporation over the first hole-transport layer to a thickness of 40 nm such that the weight ratio of 11mDBtBPPnfpr to β NCCP-d.sub.26 to OCPG-006 was 0.4:0.6:0.05, whereby the first light-emitting layer was formed.

[0668] Next, 9-[3-(4,6-diphenyl-1,3,5-triazin-2-yl)phenyl]-9'-phenyl-2,3'-bi-9H-carbazole (abbreviation: mPCCzPTzn-02) represented by Structural Formula (iv) above was deposited by evaporation to a thickness of 10 nm, whereby the first electron-transport layer was formed.

[0669] After the first electron-transport layer was formed, 2,2'-(1,3-phenylene)bis(9-phenyl-1,10-phenanthroline) (abbreviation: mPPhen2P) represented by Structural Formula (v) above as the second organic compound having a phenanthroline skeleton and ytterbium (Yb) were deposited by co-evaporation to a thickness of 5 nm such that the weight ratio of mPPhen2P to Yb was 1:0.02, whereby the first layer was formed. Then, copper phthalocyanine (abbreviation: CuPc) represented by Structural Formula (vii) above was deposited by evaporation to a thickness of 2 nm, whereby

the third layer was formed. Furthermore, oFBiSF(2) and OCHD-003 were deposited by co-evaporation to a thickness of 10 nm such that the weight ratio of oFBiSF(2) to OCHD-003 was 1:0.15, whereby the second layer was formed. Thus, the intermediate layer was formed.

[0670] Over the intermediate layer, oFBiSF(2) was deposited by evaporation to a thickness of 75 nm, whereby the second hole-transport layer was formed.

[0671] Over the second hole-transport layer, 11mDBtBPPnfr, β NCCP-d.sub.26, and OCPG-006 were deposited by co-evaporation to a thickness of 40 nm such that the weight ratio of 11mDBtBPPnfr to β NCCP-d.sub.26 to OCPG-006 was 0.4:0.6:0.05, whereby the second light-emitting layer was formed.

[0672] Then, 2-[3'-(9,9-dimethyl-9H-fluoren-2-yl)biphenyl-3-yl]-4,6-diphenyl-1,3,5-triazine (abbreviation: mFBPTzn) represented by Structural Formula (viii) above was deposited to a thickness of 10 nm, and then 2,2'-[1,2-naphthalendiyl-di(4,1-phenylene)]bis(4,6-diphenyl-1,3,5-triazine) (abbreviation: TznP2N) represented by Structural Formula (ix) above and 8-hydroxyquinolino-lithium (abbreviation: Liq) represented by Structural Formula (x) above were deposited by co-evaporation to a thickness of 25 nm such that the weight ratio of TznP2N to Liq was 1:1, whereby the second electron-transport layer was formed.

[0673] After that, lithium fluoride (LiF) and ytterbium (Yb) were deposited by co-evaporation to a thickness of 1.5 nm such that the volume ratio of LiF to Yb was 2:1, and then silver (Ag) and magnesium (Mg) were deposited by co-evaporation to a thickness of 15 nm such that the volume ratio of Ag to Mg was 1:0.1, whereby the second electrode **102** was formed. Over the second electrode **102**, a film of 4,4',4''-(benzene-1,3,5-triyl)tri(dibenzothiophene) (abbreviation: DBT3P-II) represented by Structural Formula (xi) above was formed to a thickness of 70 nm as a cap layer to improve light extraction efficiency.

[0674] Next, the light-emitting device was sealed using a glass substrate in a glove box containing a nitrogen atmosphere so as not to be exposed to the air. Specifically, a UV curable sealing material was applied to surround the device, only the sealing material was irradiated with UV while the light-emitting device was not irradiated with the UV, and heat treatment was performed at 80° C. under an atmospheric pressure for one hour. In this manner, the light-emitting device **R4** was fabricated.

(Fabrication Method of Light-Emitting Device **G4**)

[0675] The light-emitting device **G4** was fabricated in a manner similar to that of the light-emitting device **R4** except that the thickness of the first hole-transport layer was changed to 90 nm, the thickness of the second hole-transport layer was changed to 65 nm, and the first light-emitting layer and the second light-emitting layer were each formed by co-evaporation of 8-(1,1':4',1''-terphenyl-3-yl-2,4,5,6,2',3',5',6',2'',3'',4'',5'',6''-d.sub.3)-4-[3-(dibenzothiophen-4-yl)phenyl]-[1]benzofuro[3,2-d]pyrimidine (abbreviation: 8mpTP-4mDBtPBfpm-d.sub.13) represented by Structural Formula (xiii) above, β NCCP-d.sub.26, and (2-{1-(5-tert-butylbiphenyl-2-yl)-4-[3-tert-butyl-5-(4-phenyl-2-pyridinyl- κ N)phenyl- κ C.sup.6]-2-benzimidazolyl- κ N.sup.3]-4,6-di-tert-butylphenolato- κ O}platinum(II) (abbreviation: Pt(tBudppymmtBubiz-tBubp)) represented by Structural Formula (xx) above such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP-d.sub.26 to Pt(tBudppymmtBubiz-tBubp) was 0.5:0.5:0.1.

(Fabrication Method of Light-Emitting Device **B4**)

[0676] The light-emitting device **B4** was fabricated in a manner similar to that of the light-emitting device **R4** except that the first hole-transport layer and the second first hole-transport layer were each formed to have a two-layer structure by depositing oFBiSF(2) by evaporation to a thickness of 40 nm and then depositing N,N-bis[4-(dibenzofuran-4-yl)phenyl]-4-amino-p-terphenyl (abbreviation: DBfBB1TP) represented by Structural Formula (xxi) above by evaporation to a thickness of 10 nm, and the first light-emitting layer and the second light-emitting layer were each formed to a thickness of 25 nm by co-evaporation of 9-(1-naphthyl)-10-[4-(2-naphthyl)phenyl]anthracene (abbreviation: α N- β NPAnth) represented by Structural Formula (xviii)

above and N,N-diphenyl-N,N-bis(9-phenyl-9H-carbazol-2-yl)naphtho[2,3-b;6,7-b']bisbenzofuran-3,10-diamine (abbreviation: 3,10PCA2Nbf(IV)-02) represented by Structural Formula (xix) above such that the weight ratio of α N- β NPAnth to 3,10PCA2Nbf(IV)-02 was 1:0.015.

[0677] The structures of the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4 are shown below.

TABLE-US-00014 TABLE 14 Thickness Light-emitting Light-emitting Light-emitting (nm) device R4 device G4 device B4 Cap layer 70 DBT3P-II Second electrode 2 15 Ag:Mg (1:0.1) 1 1.5 LIF:Yb (2:1) Second b 25 TznP2N:Liq (1:1) electron-transport layer a 10 mFBPTzn Second light-emitting layer *6 *2 Second b 10 — — DBfBB1TP hole-transport layer a *5 oFBiSF(2)

Intermediate Second layer 10 oFBiSF(2):OCHD-003 (1:0.15) layer Third layer 2 CuPc First layer 5 mPPhen2P:Yb (1:0.02) First electron-transport layer 10 mPCCzPTzn-02 First light-emitting layer *4 *2 First b 10 — — DBfBB1TP hole-transport layer a *3 oFBiSF(2) Hole-injection layer 10 oFBiSF(2):OCHD-003 (1:0.03) First electrode 2 85 ITSO 1 100 Ag

TABLE-US-00015 TABLE 15 *2 Light-emitting 11mDBtBPPnfr: β NCCP-d.sub.26:OCPG-006 device R4 (0.4:0.6:0.05) Light-emitting 8mpTP-4mDBtPBfpm-d.sub.13: β NCCP-d.sub.26:Pt(tBudppymmtBubiz-tBubp) device G4 (0.5:0.5:0.1) Light-emitting α N- β NP Anth:3,10PCA2Nbf(IV)-02 device B4 (1:0.015)

TABLE-US-00016 TABLE 16 *3 *4 *5 *6 Light-emitting 160 40 75 40 device R4 Light-emitting 90 65 device G4 Light-emitting 40 25 40 25 device B4

[0678] FIG. 47, FIG. 48, FIG. 49, FIG. 50, and FIG. 52 respectively show the luminance-current density characteristics, current efficiency-luminance characteristics, current density-voltage characteristics, power efficiency-luminance characteristics, and electroluminescence spectra of the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4. FIG. 51 shows the blue index-luminance characteristics of the light-emitting device B4.

[0679] Note that the blue index (BI) is a value obtained by dividing current efficiency (cd/A) by the y value of CIE chromaticity (x, y), and is one of the indicators of characteristics of blue light emission. As the y chromaticity value of blue light emission becomes smaller, the color purity thereof tends to be higher. Blue light emission having a small chromaticity value and high color purity enables expression of blue colors with a wide range of chromaticity in a display. Using blue light emission with high color purity reduces the luminance of blue light emission necessary for a display to express white, leading to lower power consumption of the display. Thus, BI, which is current efficiency based on a y chromaticity value as one of the indicators of color purity of blue, is suitably used as a means for showing efficiency of blue light emission in some cases. The light-emitting device with higher BI can be regarded as a blue-light-emitting device having higher efficiency for a display.

[0680] Table 17 shows the main characteristics of the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4 at approximately 1000 cd/m.². The luminance, CIE chromaticity, and electroluminescence spectra were measured at room temperature with a spectroradiometer (SR-UL1R, TOPCON TECHNOHOUSE CORPORATION).

TABLE-US-00017 TABLE 17 Current Current Power Voltage Current density Chromaticity Chromaticity efficiency efficiency BI (V) (mA) (mA/cm.²) x y (cd/A) (lm/W) (cd/A/y) Light-emitting 6.60 0.07 1.6 0.68 0.32 74.9 35.7 — device R4 Light-emitting 5.40 0.02 0.4 0.16 0.75 174.9 101.7 — device G4 Light-emitting 8.00 0.29 7.3 0.14 0.04 9.7 3.8 232.6 device B4

[0681] FIGS. 47 to 52 and Table 17 reveal that red light emission with an electroluminescence spectrum peak wavelength of 620 nm can be obtained from the light-emitting device R4, green light emission with an electroluminescence spectrum peak wavelength of 518 nm can be obtained from the light-emitting device G4, and blue light emission with an electroluminescence spectrum peak wavelength of 457 nm can be obtained from the light-emitting device B4. It was also found that the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4 have high current efficiency as light-emitting devices of the respective emission colors. The light-

emitting device R4, the light-emitting device G4, and the light-emitting device B4 were found to be tandem light-emitting devices having favorable characteristics.

[0682] Next, materials used for the light-emitting layer of the light-emitting device G4 will be described.

[0683] FIG. 39 shows the measurement results of emission spectra of an evaporated film of 8mpTP-4mDBtPBfpm-d.sub.13, an evaporated film of β NCCP-d.sub.26, and a film (a mixed film) formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP-d.sub.26 was 1:1. As shown in the graph, the emission spectrum of the co-evaporated film is on a longer wavelength side than the emission spectra of the organic compounds, which indicates that 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 form an exciplex in combination.

[0684] FIG. 53 shows an emission spectrum of a film (a mixed film) formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 such that the weight ratio of 8mpTP-4mDBtPBfpm-d.sub.13 to β NCCP-d.sub.26 was 1:1 (a PL spectrum of an exciplex) and an absorption spectrum and an emission spectrum (a PL spectrum) of Pt(tBudppymmtBubiz-tBubp), which is the emission center substance. As shown in FIG. 53, the emission edge (442 nm) on a shorter wavelength side of the PL spectrum of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 is positioned at a shorter wavelength than the absorption edge (461 nm) on a longer wavelength side of the absorption spectrum of Pt(tBudppymmtBubiz-tBubp). Since the PL spectrum of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 and the absorption edge of Pt(tBudppymmtBubiz-tBubp) have such a positional relation, excitation energy can be efficiently transferred to Pt(tBudppymmtBubiz-tBubp) in the light-emitting device G4.

[0685] Alternatively, the peak wavelength (500 nm) of the PL spectrum of the exciplex formed by 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 is shorter than the peak wavelength (552 nm) of the PL spectrum of Pt(tBudppymmtBubiz-tBubp). Since the peak wavelengths of the PL spectra of the exciplex and Pt(tBudppymmtBubiz-tBubp) have such a relation, energy can be efficiently transferred.

[0686] Note that the PL spectrum of the exciplex was measured using a film formed by co-evaporation of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26. The PL spectrum or the absorption spectrum of Pt(tBudppymmtBubiz-tBubp) was measured using a solution thereof in which chloroform was used as a solvent.

[0687] The absorption edge of the absorption spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a longer wavelength side of the longest-wavelength peak (or the longest-wavelength shoulder peak) of the absorption spectrum has the maximum absolute value. The emission edge on a shorter wavelength side of the PL spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the PL spectrum has the maximum absolute value. FIG. 54 shows an example of determining the absorption edge of the absorption spectrum of Pt(tBudppymmtBubiz-tBubp). In this manner, the absorption edge of Pt(tBudppymmtBubiz-tBubp) can be determined to be at 461 nm.

[0688] The HOMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -5.60 eV; the HOMO level of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property was -6.3 eV (reference value); the LUMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -2.19 eV; and the LUMO level of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property was -3.01 eV.

[0689] Since the HOMO level of the organic compound having a hole-transport property is higher than or equal to the HOMO level of the organic compound having an electron-transport property and the LUMO level of the organic compound having a hole-transport property is higher than or

equal to the LUMO level of the organic compound having an electron-transport property, it was found that the light-emitting device G4 can form an exciplex more efficiently.

[0690] The HOMO level and the LUMO level of Pt(tBudppymmtBubiz-tBubp) were -5.4 eV and -2.78 eV, respectively. The energy difference between the HOMO level and the LUMO level of the exciplex of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 was 2.59 eV, which corresponds to the energy difference between the HOMO level (-5.60 eV) of β NCCP-d.sub.26 as the organic compound having a hole-transport property and the LUMO level (-3.01 eV) of 8mpTP-4mDBtPBfpm-d.sub.13 as the organic compound having an electron-transport property. The energy difference (2.62 eV) between the HOMO level (-5.4 eV) and the LUMO level (-2.78 eV) corresponding to the band gap of Pt(tBudppymmtBubiz-tBubp) was found to be larger than the energy difference between the HOMO level and the LUMO level of the exciplex.

[0691] Next, materials used for a light-emitting layer of the light-emitting device R4 will be described.

[0692] FIG. 55 shows the measurement results of PL spectra of an evaporated film of 11mDBtBPPnfpr, an evaporated film of β NCCP-d.sub.26, and a film (a mixed film) formed by co-evaporation of 11mDBtBPPnfpr and β NCCP-d.sub.26 such that the weight ratio of 11mDBtBPPnfpr to β NCCP-d.sub.26 was 0.5:0.5. As shown in the graph, the PL spectrum of the co-evaporated film is on a longer wavelength side than the PL spectra of the organic compounds, which indicates that 11mDBtBPPnfpr and β NCCP-d.sub.26 form an exciplex in combination.

[0693] FIG. 56 shows a PL spectrum of a film (a mixed film) formed by co-evaporation of 11mDBtBPPnfpr and β NCCP-d.sub.26 such that the weight ratio of 11mDBtBPPnfpr to β NCCP-d.sub.26 was 0.5:0.5 (an emission spectrum of an exciplex) and an absorption spectrum and a PL spectrum of OCPG-006, which is the emission center substance. As shown in FIG. 56, the emission edge (443 nm) on a shorter wavelength side of the PL spectrum of the exciplex of 11mDBtBPPnfpr and β NCCP-d.sub.26 is positioned at a shorter wavelength than the absorption edge (622 nm) on a longer wavelength side of the absorption spectrum of OCPG-006. Since the PL spectrum of the exciplex of 11mDBtBPPnfpr and β NCCP-d.sub.26 and the absorption edge of OCPG-006 have such a positional relation, excitation energy can be efficiently transferred to OCPG-006 in the light-emitting device R4.

[0694] Alternatively, the peak wavelength (503 nm) of the PL spectrum of the exciplex formed by 11mDBtBPPnfpr and β NCCP-d.sub.26 is shorter than the peak wavelength (621 nm) of the PL spectrum of OCPG-006. Since the peak wavelengths of the PL spectra of the exciplex and OCPG-006 have such a relation, energy can be efficiently transferred.

[0695] Note that the PL spectrum of the exciplex was measured using a co-evaporated film of 11mDBtBPPnfpr and β NCCP-d.sub.26. The PL spectrum or the absorption spectrum of OCPG-006 was measured using a solution thereof in which dichloromethane was used as a solvent.

[0696] The absorption edge of the absorption spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a longer wavelength side of the longest-wavelength peak (or the longest-wavelength shoulder peak) of the absorption spectrum has the maximum absolute value. The emission edge on a shorter wavelength side of the PL spectrum was determined as the intersection between a tangent and the horizontal axis or the baseline. The tangent was drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the PL spectrum has the maximum absolute value. FIG. 57 shows an example of determining the absorption edge of the absorption spectrum of OCPG-006. In this manner, the absorption edge of OCPG-006 can be determined to be at 622 nm.

[0697] The HOMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -5.60 eV; the HOMO level of 11 mDBtBPPnfpr as the organic compound having an electron-transport property was -6.16 eV; the LUMO level of β NCCP-d.sub.26 as the organic compound having a hole-transport property was -2.19 eV; and the LUMO level of

11mDBtBPPnfr as the organic compound having an electron-transport property was -3.02 eV. Since the HOMO level of the organic compound having a hole-transport property is higher than or equal to the HOMO level of the organic compound having an electron-transport property and the LUMO level of the organic compound having a hole-transport property is higher than or equal to the LUMO level of the organic compound having an electron-transport property, it was found that the light-emitting device R4 can form an exciplex more efficiently.

[0698] The values of the HOMO level and the LUMO level were calculated in a manner similar to that in Example 1.

[0699] The T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 were measured. The T.sub.1 levels were calculated in a manner similar to that in Example 1. Note that the emission edge was determined as the intersection between a tangent and the horizontal axis (representing wavelength) or the baseline, as shown in FIGS. 43 and 45. The tangent was drawn at a point at which the slope on a shorter wavelength side of the shortest-wavelength peak (or the shortest-wavelength shoulder peak) of the emission spectrum (phosphorescent spectrum) has the maximum absolute value. As a result of the measurement, the T.sub.1 levels of 8mpTP-4mDBtPBfpm-d.sub.13 and β NCCP-d.sub.26 were 2.55 eV and 2.56 eV, respectively.

[0700] As described above, one or both of the first host material and the second host material are deuterated in the light-emitting device R4 and the light-emitting device G4. Particularly, in the light-emitting device G4, the difference in the T.sub.1 level between the first host material and the second host material is less than or equal to 0.2 eV, and the efficiency of energy transfer from the triplet excited state is improved by the influence of deuterium; thus, deterioration of the first host material and the second host material can be significantly inhibited.

[0701] The phosphorescence lifetimes of β NCCP, β NCCP-d.sub.26, 8mpTP-4mDBtPBfpm, and 8mpTP-4mDBtPBfpm-d.sub.13 and the rate of change in phosphorescence lifetime owing to deuteration are shown below. Note that the excitation wavelength of β NCCP and β NCCP-d.sub.26 was 330 nm and the measured wavelength was 515 nm. The excitation wavelength of 8mpTP-4mDBtPBfpm and 8mpTP-4mDBtPBfpm-d.sub.13 was 320 nm and the measured wavelength was 515 nm. The results show that the phosphorescence lifetime of 8mpTP-4mDBtPBfpm-d.sub.13 is 1.80 times, i.e., more than 1.50 times, the phosphorescence lifetime of 8mpTP-4mDBtPBfpm, and the phosphorescence lifetime of β NCCP-d.sub.26 is 3.18 times, i.e., more than 3.00 times, the phosphorescence lifetime of β NCCP.

TABLE-US-00018 TABLE 18 Phosphorescence Increasing rate lifetime (deuterated/ (seconds) non-deuterated)

β NCCP	1.63	3.18	β NCCP-d.sub.26	5.18	8mpTP-4mDBtPBfpm	2.98	1.80	8mpTP-4mDBtPBfpm-d.sub.13	5.35
--------------	--------	--------	-----------------------	--------	------------------	--------	--------	---------------------------	--------

[0702] Note that the phosphorescence lifetimes were measured in a manner similar to that in Example 1.

[0703] Here, the second electron-transport layers of the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4 include the same material (the first organic compound having a triazine skeleton). Thus, the light-emitting devices of different emission colors of one embodiment of the present invention can each have favorable characteristics even when the second electron-transport layers of the light-emitting devices are made of the same material.

[0704] Next, a display device of this example including the light-emitting device R4, the light-emitting device G4, and the light-emitting device B4 respectively in red, green, and blue subpixels was assumed, and the power consumption of the display portion (except for the power consumption of a driving transistor, a driving circuit, and the like) was tentatively calculated. Note that each of the light-emitting devices assumed to be used in the display device is a tandem light-emitting device, and the same emission center substance is used in a plurality of light-emitting layers in each of the light-emitting devices. Thus, the display device that includes the light-emitting devices is a display device that employs a side-by-side patterning method.

[0705] The conditions of the display devices assumed for the tentative calculation are as follows.

TABLE-US-00019 TABLE 19 Panel size 5 inches (16:9) Panel area 68.9 cm.sup.2 Aperture ratio 30% Red 10% Green 10% Blue 10% Effective luminance 1000 cd/m.sup.2 in displaying white on the entire screen Circularly polarizing plate Not used

[0706] First, in each of the display devices under the above-described conditions, the luminance (effective luminance) of the light-emitting devices of RGB to obtain 1000 cd/m.sup.2 emission of white light with CIE 1931 chromaticity coordinates (x, y)=(0.31, 0.33) when the display device is made to emit white light from the entire screen was calculated.

[0707] Next, the luminance (intrinsic luminance) required to obtain the calculated effective luminance of the light-emitting devices of RGB was calculated in consideration of the aperture ratios. The intrinsic luminance is the luminance at which each light-emitting device actually emits light in order to obtain the effective luminance of 1000 cd/m.sup.2 when the display device is made to emit white light with CIE 1931 chromaticity coordinates (x, y)=(0.31, 0.33) from the entire screen. Since the aperture ratio of the whole display device subjected to the tentative calculation is 30% and the aperture ratio per emission color is 10%, the intrinsic luminance is approximately ten times the effective luminance.

[0708] From the measurement results of the light-emitting devices described above and the intrinsic luminance, the current density and voltage for making each light-emitting device emit light at the intrinsic luminance can be obtained. In other words, in each of the display devices under the above-described conditions, the current density and voltage of each light-emitting device to obtain 1000 cd/m.sup.2 luminance emission of white light with CIE 1931 chromaticity coordinates (x, y)=(0.31, 0.33) when the display device is made to emit white light from the entire screen can be obtained.

[0709] The power consumption is calculated by multiplying the amount of current by the voltage. The amount of current is calculated by multiplying the current density, the panel area, and the aperture ratio. The display devices subjected to the tentative calculation each have a diagonal size of 5 inches, an aspect ratio of 16:9, a panel area of 68.9 cm.sup.2, and an aperture ratio of the light-emitting device of each color of 10%, and the amount of current can be calculated by multiplying the current density calculated in the previous paragraph by these values. Furthermore, power consumption of the light-emitting device of each emission color can be calculated by multiplying the amount of current by the voltage obtained in the previous paragraph. By calculating and summing up the power consumptions of the light-emitting devices of RGB, the total power consumption of the display portion of the display device (except for the power consumption of the driving transistor, the driving circuit, and the like) can be obtained.

[0710] The results of calculating the power consumption of the display device of this example assumed to include the light-emitting devices R4, G4, and B4 are shown in Table 20.

TABLE-US-00020	TABLE 20	Effective	Intrinsic	Current	Current	Power	Chromaticity
Chromaticity	luminance	luminance	efficiency	density	amount	Voltage	consumption x y
(cd/m.sup.2)	(cd/m.sup.2)	(cd/A)	(mA/cm.sup.2)	(mA)	(V)	(mW)	Red 0.68 0.32 289 2894 70.9 4.1
28.2 7.31 205.7	Green 0.16 0.75 659 6592 184.5 3.6 24.6 6.25 153.9	Blue 0.14 0.04 51 514 9.7 5.3	36.6 7.81 286.0	All white 0.31 0.33 1000 — 77.1 — 89.4 — 645.6			

[0711] Table 20 shows that the display device of this example has high current efficiency in emitting white light and low driving voltage. Moreover, the power consumption of the display device of this example is low.

[0712] Thus, the display device including the tandem light-emitting devices in each of which the light-emitting layer includes the first host material and the second host material one or both of which are deuterated and the emission center substance, the second electron-transport layer includes the first organic compound having a triazine skeleton, the intermediate layer includes the mixed layer of the second organic compound having a phenanthroline skeleton and lithium or a lithium compound, and the difference in maximum peak wavelength between the emission spectra of light emitted from the light-emitting layers is less than or equal to 30 nm has favorable

characteristics with low power consumption.

[0713] This application is based on Japanese Patent Application Serial No. 2024-036310 filed with Japan Patent Office on Mar. 8, 2024, the entire contents of which are hereby incorporated by reference.

Claims

1. A light-emitting device comprising: a first electrode; a second electrode; an intermediate layer; a first light-emitting layer; a second light-emitting layer; a first electron-transport layer; and a second electron-transport layer, wherein the intermediate layer is between the first electrode and the second electrode, wherein the first light-emitting layer is between the first electrode and the intermediate layer, wherein the second light-emitting layer is between the intermediate layer and the second electrode, wherein the first electron-transport layer is between the first light-emitting layer and the intermediate layer, wherein the second electron-transport layer is between the second light-emitting layer and the second electrode, wherein the first light-emitting layer comprises a first emission center substance, a third organic compound, and a fourth organic compound, wherein the second light-emitting layer comprises a second emission center substance, a fifth organic compound, and a sixth organic compound, wherein the third organic compound and the fifth organic compound each comprise a π -electron deficient heteroaromatic ring, wherein the fourth organic compound and the sixth organic compound each comprise a π -electron rich heteroaromatic ring or an aromatic amine skeleton, wherein one or both of the third organic compound and the fourth organic compound or one or both of the fifth organic compound and the sixth organic compound comprise deuterium, wherein a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm, wherein the first light-emitting layer emits light of a hue different from a hue of light emitted by a first light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-emitting device, and wherein the second light-emitting layer emits light of a hue different from a hue of light emitted by a second light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

2. A light-emitting device comprising: a first electrode; a second electrode; an intermediate layer; a first light-emitting layer; a second light-emitting layer; a first electron-transport layer; and a second electron-transport layer, wherein the intermediate layer is between the first electrode and the second electrode, wherein the first light-emitting layer is between the first electrode and the intermediate layer, wherein the second light-emitting layer is between the intermediate layer and the second electrode, wherein the first electron-transport layer is between the first light-emitting layer and the intermediate layer, wherein the second electron-transport layer is between the second light-emitting layer and the second electrode, wherein the first light-emitting layer comprises a first emission center substance, a third organic compound, and a fourth organic compound, wherein the second light-emitting layer comprises a second emission center substance, a fifth organic compound, and a sixth organic compound, wherein the third organic compound and the fifth organic compound each comprise a π -electron deficient heteroaromatic ring, wherein the fourth organic compound and the sixth organic compound each comprise a π -electron rich heteroaromatic ring or an aromatic amine skeleton, wherein one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound comprise deuterium, wherein a difference between a maximum peak wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm, wherein the first light-emitting layer emits light of a hue different from a hue of light emitted by a first light-emitting layer of at least one of a plurality of light-emitting devices adjacent to the light-

emitting device, and wherein the second light-emitting layer emits light of a hue different from a hue of light emitted by a second light-emitting layer of the at least one of the plurality of light-emitting devices adjacent to the light-emitting device.

3. The light-emitting device according to claim 1, wherein the second electron-transport layer comprises a first organic compound comprising a triazine skeleton, and wherein the intermediate layer comprises a mixed layer of a second organic compound comprising a phenanthroline skeleton and one of lithium and a lithium compound.

4. The light-emitting device according to claim 2, wherein the second electron-transport layer comprises a first organic compound comprising a triazine skeleton, and wherein the intermediate layer comprises a mixed layer of a second organic compound comprising a phenanthroline skeleton and one of lithium and a lithium compound.

5. The light-emitting device according to claim 1, wherein the intermediate layer comprises lithium or a lithium compound.

6. The light-emitting device according to claim 5, wherein the intermediate layer comprises a mixed layer of a second organic compound and one of the lithium and the lithium compound.

7. The light-emitting device according to claim 1, wherein the third organic compound and the fourth organic compound form a first exciplex, and wherein the fifth organic compound and the sixth organic compound form a second exciplex.

8. The light-emitting device according to claim 7, wherein a difference between a lowest triplet excited level of the third organic compound and a lowest triplet excited level of the fourth organic compound is less than or equal to 0.20 eV, and wherein a difference between a lowest triplet excited level of the fifth organic compound and a lowest triplet excited level of the sixth organic compound is less than or equal to 0.20 eV.

9. The light-emitting device according to claim 7, wherein an emission edge on a shorter wavelength side of a PL spectrum of the first exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of an absorption spectrum of the first emission center substance, and wherein an emission edge on a shorter wavelength side of a PL spectrum of the second exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of an absorption spectrum of the second emission center substance.

10. The light-emitting device according to claim 7, wherein a peak wavelength of an emission spectrum of the first exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the first emission center substance, wherein a difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm, wherein a peak wavelength of an emission spectrum of the second exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the second emission center substance, and wherein a difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

11. The light-emitting device according to claim 2, wherein the intermediate layer comprises lithium or a lithium compound.

12. The light-emitting device according to claim 11, wherein the intermediate layer comprises a mixed layer of a second organic compound and one of the lithium and the lithium compound.

13. The light-emitting device according to claim 2, wherein the third organic compound and the fourth organic compound form a first exciplex, and wherein the fifth organic compound and the sixth organic compound form a second exciplex.

14. The light-emitting device according to claim 13, wherein a difference between a lowest triplet excited level of the third organic compound and a lowest triplet excited level of the fourth organic compound is less than or equal to 0.20 eV, and wherein a difference between a lowest triplet excited level of the fifth organic compound and a lowest triplet excited level of the sixth organic

compound is less than or equal to 0.20 eV.

15. The light-emitting device according to claim 13, wherein an emission edge on a shorter wavelength side of a PL spectrum of the first exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of an absorption spectrum of the first emission center substance, and wherein an emission edge on a shorter wavelength side of a PL spectrum of the second exciplex is at a shorter wavelength than an absorption edge on a longer wavelength side of an absorption spectrum of the second emission center substance.

16. The light-emitting device according to claim 13, wherein a peak wavelength of an emission spectrum of the first exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the first emission center substance, wherein a difference between the peak wavelength of the emission spectrum of the first exciplex and the peak wavelength of the emission spectrum of the first emission center substance is less than or equal to 30 nm, wherein a peak wavelength of an emission spectrum of the second exciplex is on a shorter wavelength side than a peak wavelength of the emission spectrum of the second emission center substance, and wherein a difference between the peak wavelength of the emission spectrum of the second exciplex and the peak wavelength of the emission spectrum of the second emission center substance is less than or equal to 30 nm.

17. A display device comprising: a first light-emitting device; and a second light-emitting device, wherein the first light-emitting device and the second light-emitting device are adjacent to each other, wherein the first light-emitting device comprises: a first electrode; a second electrode; a first intermediate layer; a first light-emitting layer; a second light-emitting layer; a first electron-transport layer; and a second electron-transport layer, wherein the first intermediate layer is between the first electrode and the second electrode, wherein the first light-emitting layer is between the first electrode and the first intermediate layer, wherein the second light-emitting layer is between the first intermediate layer and the second electrode, wherein the first electron-transport layer is between the first light-emitting layer and the first intermediate layer, wherein the second electron-transport layer is between the second light-emitting layer and the second electrode, wherein the second light-emitting device comprises: a third electrode; a fourth electrode; a second intermediate layer; a third light-emitting layer; a fourth light-emitting layer; a third electron-transport layer; and a fourth electron-transport layer, wherein the second intermediate layer is between the third electrode and the fourth electrode, wherein the third light-emitting layer is between the third electrode and the second intermediate layer, wherein the fourth light-emitting layer is between the second intermediate layer and the fourth electrode, wherein the third electron-transport layer is between the third light-emitting layer and the second intermediate layer, wherein the fourth electron-transport layer is between the fourth light-emitting layer and the fourth electrode, wherein the second electron-transport layer and the fourth electron-transport layer each comprise a first organic compound comprising a triazine skeleton, wherein the second electron-transport layer and the fourth electron-transport layer are made of the same material, wherein the first intermediate layer and the second intermediate layer each comprise one of lithium and a lithium compound and a second organic compound comprising a phenanthroline skeleton, wherein the first light-emitting layer comprises a first emission center substance, a third organic compound, and a fourth organic compound, wherein the second light-emitting layer comprises a second emission center substance, a fifth organic compound, and a sixth organic compound, wherein the third organic compound and the fifth organic compound each comprise a π -electron deficient heteroaromatic ring, wherein the fourth organic compound and the sixth organic compound each comprise a π -electron rich heteroaromatic ring or an aromatic amine skeleton, wherein one or both of the third organic compound and the fourth organic compound and one or both of the fifth organic compound and the sixth organic compound comprise deuterium, wherein the third light-emitting layer comprises a third emission center substance, wherein the fourth light-emitting layer comprises a fourth emission center substance, wherein a difference between a maximum peak

wavelength of an emission spectrum of the first emission center substance and a maximum peak wavelength of an emission spectrum of the second emission center substance is less than or equal to 30 nm, wherein a difference between a maximum peak wavelength of an emission spectrum of the third emission center substance and a maximum peak wavelength of an emission spectrum of the fourth emission center substance is less than or equal to 30 nm, wherein the first light-emitting layer emits light of a hue different from a hue of light emitted by the third light-emitting layer, and wherein the second light-emitting layer emits light of a hue different from a hue of light emitted by the fourth light-emitting layer.

18. The display device according to claim 17, wherein the third organic compound and the fourth organic compound form a first exciplex, and wherein the fifth organic compound and the sixth organic compound form a second exciplex.
