

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12406923

Kind Code

B2

Date of Patent

September 02, 2025

Inventor(s)

Chang; Meng-Sheng et al.

One-time-programmable memory device including an antifuse structure and methods of forming the same

Abstract

A one time programmable memory device includes a field effect transistor and an antifuse structure. A first node of the antifuse structure includes, or is electrically connected to, the drain region of the field effect transistor. The antifuse structure includes an antifuse dielectric layer and a second node on, or over, the antifuse dielectric layer. One of the first node and the second node includes the drain region or a metal via structure formed within a via cavity extending through an interlayer dielectric material layer that overlies the field effect transistor.

Inventors: Chang; Meng-Sheng (Chu-bei, TW), Huang; Chia-En (Xinfeng Township, TW), Wang; Yih (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Company Limited (Hsinchu, TW)

Family ID: 77228166

Assignee: Taiwan Semiconductor Manufacturing Company Limited (Hsinchu, TW)

Appl. No.: 17/854008

Filed: June 30, 2022

Prior Publication Data

Document Identifier

Publication Date

US 20220328507 A1

Oct. 13, 2022

Related U.S. Application Data

division parent-doc US 16901038 20200615 US 11605639 child-doc US 17854008

Publication Classification

Int. Cl.: H01L23/525 (20060101); H01L21/28 (20250101); H10B20/25 (20230101)

U.S. Cl.:

CPC H01L23/5252 (20130101); H01L21/28008 (20130101); H10B20/25 (20230201);

Field of Classification Search

CPC: H01L (23/5252); H01L (21/28008); H10B (20/25)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5134457	12/1991	Hamdy	257/530	H01L 23/5252
5565702	12/1995	Tamura et al.	N/A	N/A
9589970	12/2016	Tseng et al.	N/A	N/A
9659943	12/2016	Tran	N/A	H10D 30/696
2006/0221698	12/2005	Obuchi	N/A	N/A
2008/0019165	12/2007	Lin	257/E29.345	G11C 17/04
2012/0176226	12/2011	Mackenzie	29/25.42	G08B 13/2437
2014/0054712	12/2013	Jung	257/368	H01L 21/28008
2016/0099251	12/2015	Yamamoto	257/350	H01L 23/5252
2017/0301681	12/2016	Denorme et al.	N/A	N/A
2019/0123056	12/2018	Cheng et al.	N/A	N/A
2020/0185371	12/2019	Zhang	N/A	N/A
2020/0212054	12/2019	Lee	N/A	H10B 20/25

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
201924056	12/2018	TW	N/A
202008601	12/2019	TW	N/A

OTHER PUBLICATIONS

TW Patent and Trademark Office; TW Application No. 110107367; Office Action mailed Jun. 17, 2024; 8 pages. cited by applicant

Primary Examiner: Gray; Aaron J

Attorney, Agent or Firm: The Marbury Law Group, PLLC

Background/Summary

RELATED APPLICATIONS (1) This application is a divisional application of U.S. application Ser. No. 16/901,038 entitled “One-Time Programmable Memory Device Including an Antifuse

BACKGROUND

(1) An one-time-programmable (OTP) memory device is a memory device that may be programmed once for permanent storage of key information in a semiconductor device. OTP memory devices include electrical fuses and electrical antifuses. Electrical fuses provide reduced device resistance upon programming. Electrical antifuses provide increased device resistance upon programming.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. 1A-1D are sequential vertical cross-sectional views during formation of a first exemplary structure of a one time programmable (OTP) memory device according to a first embodiment of the present disclosure.

(3) FIG. 1E is a vertical cross-sectional view of a first alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure.

(4) FIG. 1F is a vertical cross-sectional view of a second alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure.

(5) FIG. 1G is a vertical cross-sectional view of a third alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure.

(6) FIGS. 2A-2D are sequential vertical cross-sectional views during formation of a second exemplary structure of an OTP memory device according to a second embodiment of the present disclosure.

(7) FIG. 2E is a vertical cross-sectional view of a second alternative embodiment of the second exemplary structure according to the second embodiment of the present disclosure.

(8) FIG. 2F is a vertical cross-sectional view of a second alternative embodiment of the second exemplary structure according to the second embodiment of the present disclosure.

(9) FIG. 2G is a vertical cross-sectional view of a third alternative embodiment of the second exemplary structure according to the first embodiment of the present disclosure.

(10) FIGS. 3A-3E are vertical cross-sectional views of various embodiments of a third exemplary structure including an OTP memory device according to a third embodiment of the present disclosure.

(11) FIGS. 4A-4D are vertical cross-sectional views of various embodiments of a fourth exemplary structure including an OTP memory device according to a fourth embodiment of the present disclosure.

(12) FIGS. 5A and 5B are vertical cross-sectional views of various embodiments of a fifth exemplary structure including an OTP memory device according to a fifth embodiment of the present disclosure.

(13) FIG. 6 is a vertical cross-sectional view of a sixth exemplary structure including an OTP memory device according to a sixth embodiment of the present disclosure.

(14) FIGS. 7A and 7B are vertical cross-sectional views of various embodiments of a seventh exemplary structure including an OTP memory device according to a seventh embodiment of the present disclosure.

(15) FIGS. 8A-8C are sequential vertical cross-sectional views during formation of an eighth

exemplary structure including an OTP memory device according to an eighth embodiment of the present disclosure.

(16) FIGS. **9A-9D** are sequential vertical cross-sectional views of a ninth exemplary structure during formation of an OTP memory device according to a ninth embodiment of the present disclosure.

(17) FIGS. **10A** and **10B** are vertical cross-sectional views of various embodiments of a tenth exemplary structure including an OTP memory device according to a tenth embodiment of the present disclosure.

(18) FIGS. **11A** and **11B** are vertical cross-sectional views of various embodiments of an eleventh exemplary structure including an OTP memory device according to an eleventh embodiment of the present disclosure.

(19) FIG. **12A** is a circuit schematic of an unprogrammed discrete OTP memory device according to an embodiment of the present disclosure.

(20) FIG. **12B** is a circuit schematic of a programmed discrete OTP memory device according to an embodiment of the present disclosure.

(21) FIG. **13** is a circuit schematic of a two-dimensional array of OTP memory devices according to an embodiment of the present disclosure.

(22) FIG. **14** is a circuit schematic of a 32×2 bit cell block in which each pair of OTP memory devices shares a respective source line according to an embodiment of the present disclosure.

(23) FIG. **15** is another circuit schematic of the 32×2 bit cell block of FIG. **14** in which control switches are expressly illustrated according to an embodiment of the present disclosure.

(24) FIG. **16** is a first flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

(25) FIG. **17** is a second flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

(26) FIG. **18** is a third flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

(27) FIG. **19** is a fourth flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

(28) FIG. **20** is a fifth flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

(29) FIG. **21** is a sixth flow chart illustrating a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure.

DETAILED DESCRIPTION

(30) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(31) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or

at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. Unless explicitly stated otherwise, each element having the same reference numeral is presumed to have the same material composition and to have a thickness within a same thickness range.

(32) The present disclosure is directed generally to semiconductor devices, and specifically to an one time programmable (OTP) memory device including an antifuse structure and methods of forming the same. The present disclosure is directed generally to semiconductor devices including semiconductor-on-insulator (SOI) field effect transistors located on a same SOI substrate and having different thicknesses for body regions and methods of forming the same. A top semiconductor layer of an SOI substrate may be patterned into multiple body regions that are laterally surrounded by a shallow trench isolation structure. The different body regions may be selectively thinned using a combination of patterned oxidation mask structures and oxidation processes that oxide upper portions of unmasked body regions, or using a combination of patterned etch mask structures and etch processes that etch upper portions of unmasked body regions. The various embodiments of which are discussed in detail herebelow.

(33) Generally, an antifuse structure includes a first node and a second node that can conduct electricity, and an antifuse dielectric layer located between the first node and the second node. If the antifuse dielectric layer is in an intact structure without any rupture therethrough, the antifuse structure is in a high resistance state, or in an “unprogrammed state.” If the antifuse dielectric layer is ruptured or disturbed due to the application of a high voltage bias between the first node and the second node, a conductive material of the first node or the second node fills the rupture or disturbance to provide a conductive path through the ruptured or disturbed antifuse dielectric layer. In this case, the antifuse structure is in a low resistance state, or in a “programmed state.”

(34) FIGS. 1A-1D are sequential vertical cross-sectional views during formation of a first exemplary structure of a one time programmable (OTP) memory device according to a first embodiment of the present disclosure. Referring to FIG. 1A, a first exemplary structure for forming a one time programmable (OTP) memory device according to a first embodiment of the present disclosure is illustrated. The first exemplary structure includes a substrate **8**, which includes a substrate semiconductor layer **9**. The substrate semiconductor layer **9** includes a semiconductor material such as single crystalline silicon.

(35) A transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** may be formed on the substrate **8**. The source region **32** and the drain region **34** may be formed within the substrate semiconductor layer **9**, or may be formed in a semiconductor material portion **10** such as a doped well that is formed within the substrate semiconductor layer **9**. A dielectric gate spacer **56** may laterally surround the gate electrode **52** and/or may contact a top surface of the substrate **8**. A shallow trench isolation structure **12** may be formed in the substrate **8**, and may laterally surround the area of the field effect transistor.

(36) In an illustrative example, the semiconductor material region **10** may have a first conductivity type (such as p-type or n-type), and the substrate semiconductor layer **9** may have a doping of the first conductivity type or a second conductivity type that is the opposite of the first conductivity type. Alternatively, a triple well configuration may be used, in which the semiconductor material portion **10** is a doped well having a doping of the first conductivity type and may be formed in another doped well (not shown) having a doping of the second conductivity type and formed in the substrate semiconductor layer **9**, which may have a doping of the first conductivity type. Generally, a first p-n junction is formed between the source region **32** and the semiconductor material portion **10**, and a second p-n junction is formed between the drain region **34** and the semiconductor material portion **10**. As such, the semiconductor material portion **10** includes a body region of the field effect transistor.

(37) Referring to FIG. 1B, an antifuse dielectric layer **60** may be formed by deposition of a dielectric material layer over the drain region **34** and over the gate stack (**50**, **52**), by applying and

patterning a photoresist layer over the dielectric material layer, and by transferring the pattern in the photoresist layer through the dielectric material layer. The photoresist layer may be subsequently removed, for example, by ashing. A remaining portion of the dielectric material layer includes the antifuse dielectric layer **60**. The lateral extent of the antifuse dielectric layer **60** may cover all of the physically exposed top surface of the drain region **34**, or may cover only a portion of the physically exposed top surface of the drain region **34**. In an alternative embodiment, patterning of the dielectric material layer into the antifuse dielectric layer **60** may be performed at a subsequently processing step during patterning of the drain-side metallic material portion.

(38) According to an embodiment of the present disclosure, the drain region **34** may constitute a first node of a one time programmable (OTP) memory device, and an antifuse dielectric layer **60** may be formed directly on a top surface of the drain region **34**. The antifuse dielectric layer **60** operates as an inter-electrode dielectric that may function as an insulating structure until a threshold voltage (which is a minimum programming voltage) is applied thereacross. The antifuse dielectric layer **60** operates as a resistive material portion after a dielectric breakdown that occurs when the voltage applied thereacross exceeds the threshold voltage. Thus, the antifuse dielectric layer **60** includes a material that may have a dielectric breakdown upon application of a programming voltage during a programming step.

(39) The antifuse dielectric layer **60** may include a dielectric material such as silicon oxide, silicon oxynitride, silicon nitride, silicon carbide nitride, a dielectric metal oxide, or a stack or a combination thereof. Other suitable dielectric materials for the antifuse dielectric layer **60** are within the contemplated scope of disclosure. In one embodiment, the antifuse dielectric layer **60** may include a dielectric material different from the dielectric material of the gate dielectric **50**. In one embodiment, the antifuse dielectric layer **60** may include a metal oxide dielectric material that includes oxide vacancies such as titanium oxide to facilitate dielectric breakdown during programming. In another embodiment, the antifuse dielectric layer **60** may include silicon oxide. The thickness of the antifuse dielectric layer **60** may be in a range from 1 nm to 10 nm, such as from 2 nm to 4 nm, although lesser and greater thicknesses may also be used.

(40) Referring to FIG. **1C**, metallic material portions (**42**, **44**) may be deposited on the source region **32** and the antifuse dielectric layer **60** (which is in turn formed on the drain region **34**). For example, a metallic material layer may be deposited over the entirety of the first exemplary structure, and a photoresist layer (not shown) may be applied and patterned over the metallic material layer to form discrete patterned photoresist material portions overlying the source region **32** and/or the antifuse dielectric layer **60**. An etch process (such as a reactive ion etch process) may be performed to remove unmasked portions of the metallic material layer. A portion of the metallic material layer that remains on the source region **32** comprises the source-side metallic material portion **42**, and a portion of the metallic material layer that remains on the antifuse dielectric layer **60** comprises the drain-side metallic material portion **44**. The photoresist material portions may be subsequently removed, for example, by ashing.

(41) Alternatively, a patterned photoresist layer (not shown) including openings in areas of the source region **32** and the antifuse dielectric layer **60** may be formed over the first exemplary structure, and a metallic material may be anisotropically deposited, for example, by physical vapor deposition (PVD). A portion of the metallic material that may be deposited on the source region **32** comprises the source-side metallic material portion **42**, and a portion of the metallic material that may be deposited on the antifuse dielectric layer **60** comprises the drain-side metallic material portion **44**. The photoresist layer and portions of the metallic material deposited over the photoresist layer may be removed, for example, by a liftoff process.

(42) In one embodiment, the source-side metallic material portion **42** and the drain-side metallic material portion **44** may include a diffusion barrier metallic material that may block diffusion of metal into a semiconductor material. For example, the source-side metallic material portion **42** and the drain-side metallic material portion **44** may include at least one conductive metallic nitride

material such as TiN, TaN, WN, TiC, TaC, and/or WC. Other suitable metallic materials are within the contemplated scope of disclosure.

(43) Alternatively, the source-side metallic material portion **42** and the drain-side metallic material portion **44** may include a metal-semiconductor alloy such as a metal silicide (such as titanium silicide, tungsten silicide, cobalt silicide, nickel silicide, platinum silicide, etc.), a metal germanide, and/or a metal germanosilicide. In this embodiment, the material of the source-side metallic material portion **42** and the drain-side metallic material portion **44** may be deposited as the metal-semiconductor alloy, or may be deposited in a layer stack of at least one semiconductor layer and at least one metal layer, and may be subsequently converted into the metal-semiconductor alloy by performing an anneal process.

(44) The drain-side metallic material portion **44** may function as a second node of an antifuse structure. In this embodiment, the antifuse structure (**34**, **60**, **44**) includes a first node comprising the drain region **34**, an antifuse dielectric layer **60**, and a second node comprising the drain-side metallic material portion **44**. In one embodiment, the source-side metallic material portion **42** and the drain-side metallic material portion **44** may have the same material composition and the same thickness, which may be in a range from 2 nm to 60 nm, such as from 5 nm to 30 nm, although lesser and greater thicknesses may also be used. In another embodiment, the source-side metallic material portion **42** and the drain-side metallic material portion **44** may have different material compositions.

(45) In one embodiment, the antifuse dielectric layer **60** has a lateral extent that is greater than, or the same as, the lateral extent of the drain-side metallic material portion **44**. The antifuse dielectric layer **60** may laterally extend from an outer sidewall of the dielectric gate spacer **56** at least to an edge of a top surface of a shallow trench isolation structure **12**. In one embodiment, the patterning of the drain-side metallic material portion **44** and the antifuse dielectric layer **60** may be performed using a same patterning mask (such as a patterned photoresist layer) after deposition of the metallic material of the drain-side metallic material portion **44**. In this embodiment, the drain-side metallic material portion **44** and the antifuse dielectric layer **60** may have the same lateral extent. A periphery of the top surface of the antifuse dielectric layer **60** may coincide with a periphery of the bottom surface of the drain-side metallic material portion **44**.

(46) Referring to FIG. **1D**, an interlayer dielectric (ILD) material layer may be deposited over the gate stack (**50**, **52**), the source-side metallic material portion **42**, and the drain-side metallic material portion **44**. An ILD material layer refers to any dielectric material layer that has formed therein any metal interconnect structure, which may be a metal via structure, a metal line structure, or an integrated line and via structure. The ILD material layer that is deposited over the gate stack (**50**, **52**), the source-side metallic material portion **42**, and the drain-side metallic material portion **44** is herein referred to as a contact-level dielectric layer **70**. The contact-level dielectric layer **70** may include a dielectric material such as undoped silicate glass, a doped silicate glass, organosilicate glass, silicon carbide nitride, or other ILD dielectric material known in the art.

(47) The contact-level dielectric layer **70** may be deposited by chemical vapor deposition (CVD) or by spin coating. The top surface of the contact-level dielectric layer **70** may be formed as a planar horizontal surface (in embodiments in which a spin coating is used to deposit the contact-level dielectric layer **70**), or may be planarized by a planarization process such as a chemical mechanical planarization (CMP) process. The top surface of the contact-level dielectric layer **70** may be formed above the horizontal plane including the top surface of the gate electrode **52**. The thickness of the contact-level dielectric layer **70** may be in a range from 200 nm to 600 nm, although lesser and greater thicknesses may also be used.

(48) A photoresist layer (not shown) may be applied over the contact-level dielectric layer **70**, and may be lithographically patterned to form openings in areas that overlie the source-side metallic material portion **42**, the drain-side metallic material portion **44**, or the gate stack (**50**, **52**). An anisotropic etch process may be performed to form via cavities in areas that underlie the openings

in the photoresist layer. A top surface of the source-side metallic material portion **42**, the drain-side metallic material portion **44**, or the gate electrode **52** may be physically exposed at the bottom of each via cavity. The photoresist layer may be subsequently removed, for example, by ashing.

(49) At least one conductive material may be deposited in the via cavities. The at least one conductive material may include, for example, a metallic barrier material layer (such as a layer of TiN, TaN, WN, TiC, TaC, and/or WC) and a metallic fill material (such as W, Cu, Co, Mo, Ru, or a combination thereof). Other suitable conductive and metallic fill materials are within the contemplated scope of disclosure. Excess portions of the at least one conductive material may be removed from above the horizontal plane including the top surface of the contact-level dielectric layer **70** by a planarization process such as a chemical mechanical planarization (CMP) process and/or a recess etch process.

(50) Remaining portions of the at least one conductive material include a source-side contact via structure **72** contacting a top surface of the source-side metallic material portion **42**, a drain-side contact via structure **74** contacting a top surface of the drain-side metallic material portion **44**, and a gate contact via structure (not illustrated) contacting a top surface of the gate electrode **52**. Each of the source-side contact via structure **72**, the drain-side contact via structure **74**, and the gate contact via structure may have a respective top surface located within a same horizontal plane as the top surface of the contact-level dielectric layer **70**.

(51) Another ILD material layer, which is herein referred to as a first-line-level dielectric layer **80**, may be formed over the contact-level dielectric layer **70**. The first-line-level dielectric layer **80** may include any ILD dielectric material that may be used for the contact-level dielectric layer **70**. The ILD dielectric material of the first-line-level dielectric layer **80** may be porous or non-porous. The thickness of the first-line-level dielectric layer **80** may be in a range from 100 nm to 300 nm, although lesser and greater thicknesses may also be used.

(52) Line cavities may be formed in the first-line-level dielectric layer **80**, for example, by application and patterning of a photoresist layer (not shown) over the first-line-level dielectric layer **80** and by transfer of the pattern in the photoresist layer through the first-line-level dielectric layer **80** by an anisotropic etch process. At least one conductive material (such as a metallic barrier liner and a metallic fill material) may be deposited in the line cavities to form various metal line structures, which include a first-line-level source-side line structure **82** contacting the source-side contact via structure **72**, a first-line-level drain-side line structure **84** contacting the drain-side contact via structure **74**, and a first-line-level gate connection line structure (not illustrated) contacting the gate contact via structure.

(53) In the first exemplary OTP memory device of FIG. **1D**, the antifuse structure (**34**, **60**, **44**) includes a first node, an antifuse dielectric layer **60** located on, and over the first node. The antifuse structure also includes a second node located on, and over, the antifuse dielectric layer **60**. The first node comprises the drain region **34**, and the second node comprises the drain-side metallic material portion **44** that is vertically spaced from the first node (i.e., drain region **34**). The antifuse dielectric layer **60** located between the first node (i.e., drain region **34**) and the second node (i.e., drain-side metallic material portion **44**).

(54) The source-side metallic material portion **42** comprising the same metallic material as, and may have the same thickness as, the drain-side metallic material portion **44**. The source-side metallic material portion **42** electrically contacts the top surface of the source region **32**. The source-side contact via structure **72** electrically contacts the top surface of the source-side metallic material portion **42**. The drain-side contact via structure **74** electrically contacts the top surface of the drain-side metallic material portion **44**. An ILD material layer such as the contact-level dielectric layer **70** laterally surrounds and has formed therein, the source-side metallic material portion **42**, the drain-side metallic material portion **44**, the source-side contact via structure **72**, the drain-side contact via structure **74**, and the gate electrode **52**.

(55) The drain-side metallic material portion **44** may have a greater lateral extent than the drain-

side contact via structure **74**, and the source-side metallic material portion **42** may have a greater lateral extent than the source-side contact via structure **72**. The source-side contact via structure **72** and the drain-side contact via structure **74** may have a respective top surface within the same horizontal plane as the top surface of the contact-level dielectric layer **70**.

(56) Referring to FIG. **1E**, a first alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure may be derived from the first exemplary structure of FIG. **1D** by patterning the drain-side metallic material portion **44** inside the periphery of the top surface of the antifuse dielectric layer **60**. In this embodiment, the antifuse dielectric layer **60** may have a lateral extent that is greater than the lateral extent of the drain-side metallic material portion **44**. The periphery of a top surface of the antifuse dielectric layer **60** may be laterally offset outward from the periphery of the bottom surface of the drain-side metallic material portion **44**.

(57) Referring to FIG. **1F**, a second alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure may be derived from the first exemplary structure of FIG. **1D** by forming the drain-side metallic material portion **44** over an area that is greater than the area of the antifuse dielectric layer **60**. In this embodiment, the antifuse dielectric layer **60** may have a lateral extent that is lesser than the lateral extent of the drain-side metallic material portion **44**. The lesser extent of the antifuse dielectric layer **60** may be provided by using an etch stop dielectric layer **62** laterally surrounding the antifuse dielectric layer **60**. For example, an etch stop dielectric layer **62** including a higher dielectric breakdown electrical field strength than the material of the antifuse dielectric layer **60** may be formed over the drain region **34** by deposition and patterning of an etch stop dielectric material. The etch stop dielectric layer **62** may be formed with an opening having a lesser area than the area of a physically exposed surface of the drain region **34**. A dielectric material having a lower dielectric breakdown electrical field strength may be deposited in the opening in the etch stop dielectric layer **62** to form the antifuse dielectric layer **60**. For example, the dielectric material having the lower dielectric breakdown electrical field strength may be conformally deposited to fill the opening, and may be recessed to remove portions located outside the opening in the etch stop dielectric layer **62**. In this embodiment, the antifuse dielectric layer **60** may be located entirely within the opening through the etch stop dielectric layer **62**. In an illustrative example, the etch stop dielectric layer **62** may include a dielectric metal oxide, and the antifuse dielectric layer **60** may include silicon oxide.

(58) Referring to FIG. **1G**, a third alternative embodiment of the first exemplary structure according to the first embodiment of the present disclosure may be derived from the second alternative embodiment of the first exemplary structure of FIG. **1F** by patterning the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** includes a peripheral portion that extends outside the opening in the etch stop dielectric layer **62** and overlies the etch stop dielectric layer **62**.

(59) Referring to FIGS. **1A-1G**, a one time programmable (OTP) memory device may be provided by forming a field effect transistor (FET) including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** on a substrate **8**, and by forming an antifuse structure (**34**, **60**, **44**) including a first node comprising a drain region **34**, an antifuse dielectric layer **60** located on, and over the drain region **34**. The antifuse structure (**34**, **60**, **44**) further comprising a second node comprising the drain-side metallic material portion **44** on, and over, the antifuse dielectric layer **60**. The one time programmable (OTP) memory device may comprise a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** and located on a substrate **8**. The OTP memory device further comprising a semiconductor-insulator-metal (SIM) antifuse structure including the drain region **34** that constitutes a first node, a drain-side metallic material portion **44** that constitutes a second node that is spaced from the first node, and an antifuse dielectric layer **60** located between the first node and the second node.

(60) FIGS. **2A-2D** are sequential vertical cross-sectional views during formation of a second exemplary structure of an OTP memory device according to a second embodiment of the present

disclosure. Referring to FIG. 2A, a second exemplary structure for formation of an OTP memory device according to a second embodiment of the present disclosure is illustrated. The initial structure for formation of the OTP memory device of the second embodiment, which may start from a structure identical to the starting first exemplary structure of FIG. 1A.

(61) Referring to FIG. 2B, a source-side metallic material portion **42** and a drain-side metallic material portion **44** may be formed on the top surface of the source region **32** and on the top surface of the drain region **34**, respectively. The same processing step may be used as the processing steps of FIG. 1C for forming the source-side metallic material portion **42** and a drain-side metallic material portion **44**. The drain-side metallic material portion **44** may be formed directly on a top surface of the drain region **34**. In contrast to the first exemplary structure, the antifuse dielectric layer **60** is not formed under the drain-side metallic material portion **44**.

(62) Referring to FIG. 2C, an antifuse dielectric layer **60** may be formed by deposition of a dielectric material layer over the drain-side metallic material portion **44** and over the gate stack (**50**, **52**), by applying and patterning a photoresist layer (not shown) over the dielectric material layer, and by transferring the pattern in the photoresist layer through the dielectric material layer. The photoresist layer may be subsequently removed, for example, by ashing. A remaining portion of the dielectric material layer includes the antifuse dielectric layer **60**. The lateral extent of the antifuse dielectric layer **60** may cover the entire area of the top surface of the drain-side metallic material portion **44**, or may over only a portion of the top surface of the drain-side metallic material portion **44**.

(63) According to an embodiment of the present disclosure, the drain-side metallic material portion **44** may constitute a first node of a one-time programmable (OTP) memory device, and an antifuse dielectric layer **60** may be formed directly on a top surface of the drain-side metallic material portion **44**. The antifuse dielectric layer **60** may include the same material, and may have the same thickness as, the antifuse dielectric layer **60** in the first exemplary structure (see e.g., FIGS. 1D-1G).

(64) Referring to FIG. 2D, the processing steps of FIG. 1D may be performed to form a contact-level dielectric layer **70**, via cavities vertically extending through the contact-level dielectric layer **70**, and metal via structures that fill the via cavities. In the second embodiment, the material of the contact-level dielectric layer **70** includes a different dielectric material than the dielectric material of the antifuse dielectric layer **60**. Thus, the via cavity that is formed over the antifuse dielectric layer **60** does not extend through the antifuse dielectric layer **60**, but stops on the top surface of the antifuse dielectric layer **60**. The metal via structures may include a source-side contact via structure **72** contacting a top surface of the source-side metallic material portion **42**, a drain-side contact via structure **74** contacting a top surface of the antifuse dielectric layer **60**, and a gate contact via structure (not shown) that contacts the gate electrode **52**. Each of the source-side contact via structure **72**, the drain-side contact via structure **74**, and the gate contact via structure may have a respective top surface located within a same horizontal plane as the top surface of the contact-level dielectric layer **70**.

(65) A first-line-level dielectric layer **80** and metal line structures formed therein may be formed as in the first embodiment. The metal line structures formed in the first-line-level dielectric layer **80** may include a first-line-level source-side line structure **82** contacting the source-side contact via structure **72**, a first-line-level drain-side line structure **84** contacting the drain-side contact via structure **74**, and a first-line-level gate connection line structure (not illustrated) contacting the gate contact via structure.

(66) In the second exemplary OTP memory device of FIG. 2D, the antifuse structure (**44**, **60**, **74**) includes a first node, an antifuse dielectric layer **60** located on, and over the first node. The antifuse structure (**44**, **60**, **74**) of the second exemplary structure further comprising a second node located on, and over, the antifuse dielectric layer **60**. The first node comprises the drain-side metallic material portion **44**, and the second node comprises the drain-side contact via structure **74** that is

vertically spaced from the first node by the antifuse dielectric layer **74**. The antifuse dielectric layer **60** located between the first node (i.e., drain-side metallic material portion **44**) and the second node (i.e., drain-side contact via structure **74**).

(67) The source-side metallic material portion **42** comprising the same metallic material as, and may have the same thickness as, the drain-side metallic material portion **44**. The source-side metallic material portion **42** contacts the top surface of the source region **32**. The source-side contact via structure **72** contacts the top surface of the source-side metallic material portion **42**. The drain-side metallic material portion **44** may contact the top surface of the drain region **34**. The drain-side contact via structure **74** contacts the top surface of the antifuse dielectric layer **60**. An ILD material layer such as the contact-level dielectric layer **70** laterally surrounds and has formed therein the source-side metallic material portion **42**, the drain-side metallic material portion **44**, the source-side contact via structure **72**, the antifuse dielectric layer **60**, the drain-side contact via structure **74**, and the gate electrode **52**.

(68) The drain-side metallic material portion **44** may have a greater lateral extent than the drain-side contact via structure **74**, and the source-side metallic material portion **42** may have a greater lateral extent than the source-side contact via structure **72**. The source-side contact via structure **72** and the drain-side contact via structure **74** may have a respective top surface within the same horizontal plane as the top surface of the contact-level dielectric layer **70**.

(69) Referring to FIG. 2E, a first alternative embodiment of the second exemplary structure may be derived from the second exemplary structure of FIG. 2D by forming the antifuse dielectric layer **60** to have a same lateral extent as the drain-side contact via structure **74**. For example, the topmost portion of the drain-side metallic material portion **44** may include an oxidizable metal such as titanium or ruthenium. Starting with the structure illustrated in FIG. 2B, the processing steps of FIG. 2C may be omitted. Thus, the antifuse dielectric layer **60** may be formed after formation of the via cavities by oxidizing a surface portion of the drain-side metallic material portion **44**. In this embodiment, the antifuse dielectric layer **60** may have a same lateral extent as the drain-side contact via structure **74**. Metal oxide portions formed on the source-side metallic material portion **42** or the gate electrode **52** may be removed, for example, by a masked etch process that protects the antifuse dielectric layer **60**, prior to formation of the source-side contact via structures **72**, drain-side contact via structures **74**, and gate contact via structures.

(70) Referring to FIG. 2F, a second alternative embodiment of the second exemplary structure may be derived from the second exemplary structure of FIG. 2D by forming the drain-side contact via structure **74** over an area that is greater than the area of the antifuse dielectric layer **60**. In this embodiment, the antifuse dielectric layer **60** may have a lateral extent that is lesser than the lateral extent of the drain-side contact via structure **74**. The lesser extent of the antifuse dielectric layer **60** may be provided by using an etch stop dielectric layer **62** laterally surrounding the antifuse dielectric layer **60**. For example, an etch stop dielectric layer **62** including a higher dielectric breakdown electrical field strength than the material of the antifuse dielectric layer **60** may be formed over the drain-side metallic material portion **44** by deposition and patterning of an etch stop dielectric material. The etch stop dielectric layer **62** may be formed with an opening having a lesser area than the area of a physically exposed surface of the drain-side metallic material portion **44**. A dielectric material having a lower dielectric breakdown electrical field strength may be deposited in the opening in the etch stop dielectric layer **62** to form the antifuse dielectric layer **60**. For example, the dielectric material having the lower dielectric breakdown electrical field strength may be conformally deposited to fill the opening, and may be recessed to remove portions located outside the opening in the etch stop dielectric layer **62**. In this embodiment, the antifuse dielectric layer **60** may be located entirely within the opening through the etch stop dielectric layer **62**. In an illustrative example, the etch stop dielectric layer **62** may include a dielectric metal oxide, and the antifuse dielectric layer **60** may include silicon oxide.

(71) Referring to FIG. 2G, a third alternative embodiment of the second exemplary structure may

be derived from the second alternative embodiment of the second exemplary structure of FIG. 2F by patterning the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** includes a peripheral portion that extends outside the opening in the etch stop dielectric layer **62** and overlies the etch stop dielectric layer **62**.

(72) Referring to FIGS. 2A-2G, a one-time programmable (OTP) memory device may be provided by forming a field effect transistor (FET) including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** on a substrate **8**; and by forming an antifuse structure (**44**, **60**, **74**) including a first node comprising a drain-side metallic material portion **44**, an antifuse dielectric layer **60** located on, or over the drain-side metallic material portion **44**. The antifuse structure (**34**, **60**, **44**) further comprising a second node comprising a drain-side contact via structure **74** located on, or over, the antifuse dielectric layer **60**. The second node comprises a metal via structure formed within a via cavity extending through an interlayer dielectric material layer (such as the contact-level dielectric layer **70**) that overlies the field effect transistor. As such, the one time programmable (OTP) memory device comprises: a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** and located on a substrate **8**. The OTP memory device further comprising a metal-insulator-metal (MIM) antifuse structure (**44**, **60**, **74**) including a first node (comprising the drain-side metallic material portion **44**) electrically connected to the drain region **34**, a second node (comprising the drain-side contact via structure **74**) that is vertically spaced from the first node, and an antifuse dielectric layer **60** located between the first node and the second node, wherein the second node comprises a metal via structure that is laterally surrounded by an interlayer dielectric material layer (such as the contact-level dielectric layer **70**) that overlies the substrate **8**.

(73) In one embodiment, the first node comprises a drain-side metallic material portion **44** that is in electrical contact with the drain region **34**; and the second node comprises the metal via structure. In one embodiment, a source-side metallic material portion **42** comprising a same metallic material as the drain-side metallic material portion **44** contacts a top surface of the source region **32**. In one embodiment, the metal via structure comprises a drain-side contact via structure **74**; and an interlayer dielectric material layer (such as the contact-level dielectric layer **70**) that laterally surrounds and has formed therein, the drain-side metallic material portion **44** and the drain-side contact via structure **74**, wherein a top surface of the metal via structure is located within a horizontal plane including a top surface of the interlayer dielectric material layer.

(74) In one embodiment, the antifuse dielectric layer **60** has a lateral extent that is greater than, or the same as, a lateral extent of the second node (which may comprise the drain-side contact via structure **74**). In one embodiment, the antifuse dielectric layer **60** has a lateral extent that is less than the lateral extent of the second node (which may comprise the drain-side contact via structure **74**).

(75) Referring to FIG. 3A, a first embodiment of a third exemplary structure may be derived from the first exemplary structure of FIG. 1A by omitting the processing steps of FIG. 1B and by performing the processing steps of FIG. 1C and by performing a subset of the processing steps of FIG. 1D up to the process of formation of the source-side contact via structure **72**, the drain-side contact via structure **74**, and the gate contact via structure.

(76) An antifuse dielectric layer **60** may be formed on a top surface of the drain-side contact via structure **74** by application and patterning of a dielectric material layer. The antifuse dielectric layer **60** may have the same material composition and the same thickness as in the first embodiment. Subsequently, a first-line-level dielectric layer **80** and various metal line structures may be formed above the contact-level dielectric layer **70** and the antifuse dielectric layer **60**. The metal line structures include a first-line-level source-side line structure **82** contacting the source-side contact via structure **72**, a first-line-level drain-side line structure **84** contacting the drain-side contact via structure **74**, and a first-line-level gate connection line structure (not illustrated) contacting the gate contact via structure. The antifuse dielectric layer **60** may have a greater lateral extent than the

first-line-level drain-side line structure **84**. Thus, the antifuse structure of the third exemplary structure may comprise a first node (i.e., drain-side contact via structure **74**), antifuse dielectric layer **60**, and a second node (i.e., first-line-level drain-side line structure **84**).

(77) Referring to FIG. 3B, a second embodiment of the third exemplary structure may be derived from the first embodiment of the third exemplary structure by changing the lateral extent of the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** has a same lateral extent as the first-line-level drain-side line structure **84**.

(78) Referring to FIG. 3C, a third embodiment of the third exemplary structure may be derived from the first embodiment of the third exemplary structure of FIG. 3A by using an etch stop dielectric layer **62** laterally surrounding the antifuse dielectric layer **60**. For example, an etch stop dielectric layer **62** including a higher dielectric breakdown electrical field strength than the material of the antifuse dielectric layer **60** may be formed over the drain-side contact via structure **74** by deposition and patterning of an etch stop dielectric material. The etch stop dielectric layer **62** may be formed with an opening having a lesser area than the area of the first-line-level drain-side line structure **84** to be subsequently formed thereupon. A dielectric material having a lower dielectric breakdown electrical field strength may be deposited in the opening in the etch stop dielectric layer **62** to form the antifuse dielectric layer **60**. For example, the dielectric material having the lower dielectric breakdown electrical field strength may be conformally deposited to fill the opening, and may be recessed to remove portions located outside the opening in the etch stop dielectric layer **62**. In this embodiment, the antifuse dielectric layer **60** may be located entirely within the opening through the etch stop dielectric layer **62**. In an illustrative example, the etch stop dielectric layer **62** may include a dielectric metal oxide, and the antifuse dielectric layer **60** may include silicon oxide.

(79) Referring to FIG. 3D, a fourth embodiment of the third exemplary structure according to the third embodiment of the present disclosure may be derived from the third embodiment of the third exemplary structure of FIG. 3C by patterning the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** includes a peripheral portion that extends outside the opening in the etch stop dielectric layer **62** and overlies the etch stop dielectric layer **62**.

(80) Referring to FIG. 3E, a fifth embodiment of the third exemplary structure according to the third embodiment of the present disclosure may be derived from the first embodiment of the third exemplary structure by forming the antifuse dielectric layer **60** within a line cavity that overlies the drain-side contact via structure **74**. In this embodiment, the antifuse dielectric layer **60** may have a horizontal portion located between the drain-side contact via structure **74** and the first-line-level drain-side line structure **84**, and may have vertically-extending portions located on the sidewalls of the via cavity in the first-line-level dielectric layer **80**.

(81) Referring to FIGS. 3A-3E, a one time programmable (OTP) memory device may be provided by forming a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** on a substrate **8**; and forming an antifuse structure including a first node (comprising the drain-side contact via structure **74**), an antifuse dielectric layer **60**, and a second node (comprising a first-line-level drain-side line structure **84**) on, and over, the antifuse dielectric layer **60**. The first node comprises a metal via structure (comprising the drain-side contact via structure **74**) formed within a via cavity extending through an interlayer dielectric material layer (such as the contact-level dielectric layer **70**) that overlies the field effect transistor. The second node comprises a metal via structure (comprising the first-line-level drain-side line structure **84**) formed within a via cavity extending through an interlayer dielectric material layer (such as the first-line-level dielectric layer **80**). As such, the one time programmable (OTP) memory device may comprise: a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** and located on a substrate **8**; and a metal-insulator-metal (MIM) antifuse structure (**74**, **60**, **84**) including a first node (comprising a drain-side contact via structure **74**) electrically connected to the drain region **34**, a second node (comprising a first-line-level drain-side line structure **84**) that is vertically spaced from the first node, and an antifuse dielectric layer

60 located between the first node and the second node, wherein the first node comprises a metal via structure (comprising the drain-side contact via structure **74**) that is laterally surrounded by an interlayer dielectric material layer (such as the contact-level dielectric layer **70**) that overlies the substrate **8**.

(82) A metal line structure (such as a first-line-level drain-side line structure **84**) may be formed in another interlayer dielectric material layer (such as the first-line-level dielectric layer **80**) may be formed over the metal via structure (comprising the drain-side contact via structure **74**) and the antifuse dielectric layer **60**, wherein the first node comprises the metal via structure, and the second node comprises the metal line structure. Thus, one of the first node and the second node comprises the metal via structure (comprising the drain-side contact via structure **74**), and another of the first node and the second node comprises a metal line structure (comprising a first-line-level drain-side line structure **84**) that overlies or underlies the metal via structure.

(83) In one embodiment, the antifuse dielectric layer **60** has a lateral extent that is greater than, or the same as, a lateral extent of the second node (which may comprise the first-line-level drain-side line structure **84**). In one embodiment, the antifuse dielectric layer **60** has a lateral extent that is less than the lateral extent of the second node (comprising the first-line-level drain-side line structure **84**).

(84) Referring to FIG. **4A**, a first embodiment of a fourth exemplary structure may be derived from the third exemplary structure of FIG. **3A** by deferring formation of the antifuse dielectric layer **60** until after formation of the first-line-level drain-side line structure **84**. In this embodiment, the antifuse dielectric layer **60** may be formed directly on the top surface of the first-line-level drain-side line structure **84** by deposition and patterning of a dielectric material layer. The antifuse dielectric layer **60** may have the same material composition and the same thickness as in the first exemplary structure. Additional first-line-level metal line structures **86** may be formed in the first-line-level dielectric layer **80**. The additional first-line-level metal line structures **86** may provide electrical interconnection for various other devices that are formed on the substrate **8**.

(85) Additional ILD material layers may be deposited, and additional metal interconnect structures may be formed in the additional ILD material layers. For example, a first-via-level dielectric layer **90** may be formed over the first-line-level dielectric layer **80** and the antifuse dielectric layer **60**. The first-via-level dielectric layer **90** includes a dielectric material that may be etched selective to the material of the antifuse dielectric layer **60**. Via cavities may be formed through the first-via-level dielectric layer **90**, and may be filled with at least one conductive material to form metal via structures. The metal via structures may include a first-via-level metal via structure **94** contacting a top surface of the antifuse dielectric layer **60**, and an additional first-via-level metal via structure **96** contacting top surfaces of the additional first-line-level metal line structure **86**.

(86) A second-line-level dielectric layer **100** may be formed over the first-via-level dielectric layer **90**. Line cavities may be formed through the second-line-level dielectric layer **100**, and may be filled with at least one conductive material to form metal line structures. The metal line structures may include a second-line-level metal line structure **104** contacting a top surface of the first-via-level metal via structure **94**, and additional second-line-level metal via structure **106** contacting the additional first-via-level metal via structures **96**.

(87) Referring to FIG. **4B**, a second embodiment of the fourth exemplary structure may be derived from the first embodiment of the fourth exemplary structure by forming the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** has a same lateral extent as a bottom surface of the first-via-level metal via structure **94**. For example, the topmost portion of the first-line-level drain-side line structure **84** may include an oxidizable metal such as titanium or ruthenium. The antifuse dielectric layer **60** may be formed after formation of the via cavities through the first-via-level dielectric layer **90** by oxidizing a surface portion of the first-line-level drain-side line structure **84**. In this embodiment, the antifuse dielectric layer **60** may have a same lateral extent as the first-via-level metal via structure **94**. Metal oxide portions formed on the additional first-line-level metal

line structures **86** may be removed, for example, by a masked etch process that protects the antifuse dielectric layer **60**, prior to formation of the first-via-level metal via structure **94** and the additional first-via-level metal via structures **96**.

(88) Referring to FIG. **4C**, a third embodiment of the fourth exemplary structure may be derived from the first embodiment of the fourth exemplary structure of FIG. **4A** by using an etch stop dielectric layer **62** laterally surrounding the antifuse dielectric layer **60**. For example, an etch stop dielectric layer **62** including a higher dielectric breakdown electrical field strength than the material of the antifuse dielectric layer **60** may be formed over the first-line-level drain-side line structure **84** by deposition and patterning of an etch stop dielectric material. The etch stop dielectric layer **62** may be formed with an opening having a lesser area than the area of the first-line-level drain-side line structure **84** to be subsequently formed thereupon. A dielectric material having a lower dielectric breakdown electrical field strength may be deposited in the opening in the etch stop dielectric layer **62** to form the antifuse dielectric layer **60**. For example, the dielectric material having the lower dielectric breakdown electrical field strength may be conformally deposited to fill the opening, and may be recessed to remove portions located outside the opening in the etch stop dielectric layer **62**. In this embodiment, the antifuse dielectric layer **60** may be located entirely within the opening through the etch stop dielectric layer **62**. In an illustrative example, the etch stop dielectric layer **62** may include a dielectric metal oxide, and the antifuse dielectric layer **60** may include silicon oxide.

(89) Referring to FIG. **4D**, a fourth embodiment of the fourth exemplary structure may be derived from the third embodiment of the fourth exemplary structure of FIG. **4C** by patterning the antifuse dielectric layer **60** such that the antifuse dielectric layer **60** includes a peripheral portion that extends outside the opening in the etch stop dielectric layer **62** and overlies the etch stop dielectric layer **62**.

(90) Referring to FIG. **5A**, a first embodiment of a fifth exemplary structure may be derived from the first embodiment of the fourth exemplary structure of FIG. **4A** by deferring formation of the antifuse dielectric layer **60** until after formation of the second-line-level drain-side line structure **94**. In this embodiment, the antifuse dielectric layer **60** may be formed directly on a top surface of the first-via-level metal line structure **94**. Additional embodiments of the fifth exemplary structure may be derived from the first embodiment of the fifth exemplary structure by using the processing steps of FIG. **4B**, **4C**, or **4D** to form the antifuse dielectric layer **60** to change the lateral extent of the antifuse dielectric layer **60** relative to the lateral extent of the second-line-level metal line structure **104**.

(91) Referring to FIG. **5B**, a second embodiment of the fifth exemplary structure may be derived from the first embodiment of the fifth exemplary structure by forming the antifuse dielectric layer **60** inside a line cavity overlying the first-via-level metal via structure **94**. In this embodiment, the antifuse dielectric layer **60** may have a horizontal portion located between the first-via-level metal via structure **94** and the second-line-level metal line structure **104**, and may have vertically-extending portions located on the sidewalls of the via cavity in the second-line-level dielectric layer **100**.

(92) Referring to FIG. **6**, a sixth exemplary structure according to a sixth embodiment of the present disclosure may be derived from the first embodiment of the fourth exemplary structure by forming the antifuse dielectric layer **60** directly on a top surface of an N-th-line-level metal line structure **124** in which N is a positive integer greater than 1. Generally, an N-th-line-level dielectric layer **120** may have formed therein the N-th-line-level metal line structure **124** and additional N-th-line-level metal line structures **126**. An (N-1)-th-via-level dielectric layer **110** having formed therein (N-1)-th-via-level metal via structures **114** may be provided underneath the N-th-line-level dielectric layer **120**. The N-th-line-level metal line structure **124** may be electrically connected to the drain region **34** through the drain-side metallic material portion **44**, the first-line-level drain-side line structure **84**, the first-via-level metal via structure **94**, the (N-1)-th-via-level metal via

structures **114** (in embodiments in which N is greater than 2), and any other intervening metal interconnect structures.

(93) After formation of the antifuse dielectric layer **60**, additional ILD material layers may be deposited, and additional metal interconnect structures may be formed in the additional ILD material layers. For example, an (N-th)-via-level dielectric layer **130** may be formed over the N-th-line-level dielectric layer **120** and the antifuse dielectric layer **60**. The N-th-via-level dielectric layer **130** includes a dielectric material that may be etched selective to the material of the antifuse dielectric layer **60**. Via cavities may be formed through the N-th-via-level dielectric layer **130**, and may be filled with at least one conductive material to form metal via structures. The metal via structures may include an N-th-via-level metal via structure **134** contacting a top surface of the antifuse dielectric layer **60**, and additional N-th-via-level metal via structure **136** contacting top surfaces of the additional (N-th)-line-level metal line structure **126**.

(94) An (N+1)-th-line-level dielectric layer **140** may be formed over the N-th-via-level dielectric layer **130**. Line cavities may be formed through the (N+1)-th-line-level dielectric layer **140**, and may be filled with at least one conductive material to form metal line structures. The metal line structures may include an (N+1)-th-line-level metal line structure **144** contacting a top surface of the N-th-via-level metal via structure **134**, and additional (N+1)-th-line-level metal via structure **146** contacting the additional N-th-via-level metal via structures **136**.

(95) An antifuse structure includes a first node comprising the N-th-line-level metal line structure **124**, a second node comprising the N-th-via-level metal via structure **134**, and the antifuse dielectric layer **60**. Additional embodiments of the sixth exemplary structure may be derived from the sixth exemplary structure of FIG. 6 by using the processing steps of FIG. 4B, 4C, or 4D to form the antifuse dielectric layer **60** to change the lateral extent of the antifuse dielectric layer **60** relative to the lateral extent of the N-th-via-level metal via structure **134**.

(96) Referring to FIG. 7A, a first embodiment of a seventh exemplary structure may be derived from the sixth exemplary structure by forming the antifuse dielectric layer **60** directly on a top surface of an N-th-via-level metal via structure **134** in which N is a positive integer greater than 1. An antifuse structure includes a first node comprising the N-th-via-level metal via structure **134**, a second node comprising the (N+1)-th-line-level metal line structure **144**, and the antifuse dielectric layer **60**. Additional embodiments of the seventh exemplary structure may be derived from the first embodiment of the seventh exemplary structure of FIG. 7A by using the processing steps of FIG. 4B, 4C, or 4D to form the antifuse dielectric layer **60** to change the lateral extent of the antifuse dielectric layer **60** relative to the lateral extent of the (N+1)-th-line-level metal line structure **144**.

(97) Referring to FIG. 7B, a second embodiment of the seventh exemplary structure may be derived from the first embodiment of the seventh exemplary structure by forming the antifuse dielectric layer inside a line cavity overlying the N-th-via-level metal via structure **134**. In this embodiment, the antifuse dielectric layer **60** may have a horizontal portion located between the N-th-via-level metal via structure **134** and the (N+1)-th-line-level metal line structure **144**, and may have vertically-extending portions located on the sidewalls of the via cavity in the (N+1)-th-line-level dielectric layer **140**.

(98) Referring collectively to FIGS. 4A-7B, a one-time programmable memory device may be provided by forming a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** on a substrate **8**; and forming an antifuse structure {(84, 60, 94), (94, 60, 104), (124, 60, 134), (134, 60, 144)} including a first node (84, 94, 124, or 135), an antifuse dielectric layer **60**, and a second node (94, 104, 134, or 144) on, or over, the antifuse dielectric layer **60**, wherein one of the first node (84, 94, 124, or 135) and the second node (94, 104, 134, or 144) comprises a metal via structure (94, 134) that is formed within a via cavity extending through an interlayer dielectric material layer (90, 130) that overlies the field effect transistor. As such, the one time programmable (OTP) memory device may comprise: a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode

52 and located on a substrate 8; and a metal-insulator-metal (MIM) antifuse structure including a first node (84, 94, 124, or 135) electrically connected to the drain region 34, a second node (94, 104, 134, or 144) that is vertically spaced from the first node (84, 94, 124, or 135), and an antifuse dielectric layer 60 located between the first node (84, 94, 124, or 135) and the second node (94, 104, 134, or 144), wherein one of the first node (84, 94, 124, or 134) and the second node (94, 104, 134, or 144) comprises a metal via structure (94, 134) that is laterally surrounded by an interlayer dielectric material layer (90, 130) that overlies the substrate 8. Another of the first node (84, 94, 124, or 134) and the second node (94, 104, 134, or 144) comprises a metal line structure (84, 104, 124, 144) that overlies or underlies the metal via structure (94, 134).

(99) In some embodiments, a metal line structure (104, 144) formed in another interlayer dielectric (ILD) material layer (100, 140) may be formed over the metal via structure (104, 144) and the antifuse dielectric layer 60, wherein the first node comprises the metal via structure (94, 134), and the second node comprises the metal line structure (104, 144).

(100) In some other embodiments, the antifuse dielectric layer 60 and the metal via structure (104, 144) may be formed over a metal line structure (94, 134) that is formed in another interlayer dielectric (ILD) material layer (90, 130). The first node comprises the metal line structure (84, 124), and the second node comprises the metal via structure (94, 134).

(101) The antifuse dielectric layer 60 may have a lateral extent that is greater than, the same as, or less than, a lateral extent of the second node (94, 104, 134, or 144), i.e., the lateral extent of the bottom surface of the second node (94, 104, 134, or 144).

(102) FIGS. 8A-8C are sequential vertical cross-sectional views during formation of an eighth exemplary structure including an OTP memory device according to an embodiment of the present disclosure. Referring to FIG. 8A, an eighth exemplary structure for forming an OTP memory device may be derived from the first exemplary structure of FIG. 1A by forming an ILD material layer (which is herein referred to as a lower contact-level dielectric layer 70A) over the source-side metallic material portion 42 and the drain-side metallic material portion 44. The top surface of the lower contact-level dielectric layer 70A may be planarized to provide a horizontal top surface. For example, the top surface of the lower contact-level dielectric layer 70A may be coplanar with the top surface of the gate electrode 52.

(103) A via cavity may be formed through the lower contact-level dielectric layer 70A directly above the drain-side metallic material portion 44. The via cavity may be filled with at least one metallic material to form a metal via structure, which is herein referred to as a lower drain-side contact via structure 74A.

(104) Referring to FIG. 8B, an antifuse dielectric layer 60 may be formed on the top surface of the lower drain-side contact via structure 74A using any of the processing steps of FIG. 1B, 1F, or 1G. Another ILD dielectric layer (which is herein referred to as an upper contact-level dielectric layer 70B) may be deposited over the lower contact-level dielectric layer 70A and the antifuse dielectric layer 60. The upper contact-level dielectric layer 70B includes a dielectric material that may be etched selective to the dielectric material of the antifuse dielectric layer 60.

(105) Referring to FIG. 8C, via cavities may be formed through the upper contact-level dielectric layer 70B. An anisotropic etch process having an etch chemistry that is selective to the material of the antifuse dielectric layer 60 may be performed to form a via cavity extending down to a top surface of the antifuse dielectric layer 60. The anisotropic etch process may form another via cavity that vertically extends to a top surface of the source-side metallic material portion 42. Alternatively, an additional anisotropic etch process may be performed to form a via cavity that vertically extends to a top surface of the source-side metallic material portion 42 while the portion of the upper contact-level dielectric layer 70B overlying the antifuse dielectric layer 60 is masked by a patterned photoresist layer (not shown), which is subsequently removed.

(106) At least one metallic material may be deposited in the cavities through the upper contact-level dielectric layer 70B and the lower contact-level dielectric layer 70A. A source-side contact via

structure **72** may be formed on the source-side metallic material portion **42**, and an upper drain-side contact via structure **74B** may be formed on the antifuse dielectric layer **60**. The combination of the lower contact-level dielectric layer **70A** and the upper contact-level dielectric layer **70B** constitutes a contact-level dielectric layer **70**. A top surface of the source-side contact via structure **72** and a top surface of the upper drain-side contact via structure **74B** may be formed within a same horizontal plane as the top surface of the contact-level dielectric layer **70** (i.e., top surface of upper contact-level dielectric layer **70B**). Subsequently, a first-line-level dielectric layer **80** and metal line structures formed therein may be formed. The metal line structures may include a first-line-level source-side line structure **82** contacting the source-side contact via structure **72**, a first-line-level drain-side line structure **84** contacting the upper drain-side contact via structure **74B**, and a first-line-level gate connection line structure (not illustrated) contacting the gate contact via structure. (107) The eighth exemplary structure includes an antifuse structure (**74A**, **60**, **74B**) that includes a first node comprising the lower drain-side contact via structure **74A**, a second node comprising the upper drain-side contact via structure **74B**, and an antifuse dielectric layer **60** located between the first node and the second node.

(108) FIGS. **9A-9D** are sequential vertical cross-sectional views of a ninth exemplary structure during formation of an OTP memory device according to a ninth embodiment of the present disclosure. Referring to FIG. **9A**, a ninth exemplary structure for formation of an OTP memory device may be derived from the third exemplary structure of FIG. **3A** by modifying the step for forming the antifuse dielectric layer **60**. Specifically, the contact-level dielectric layer **70**, the source-side contact via structure **72**, and the drain-side contact via structure **74** may be formed in the same manner as in the third embodiment.

(109) Referring to FIG. **9B**, a photoresist layer **59** may be applied over the contact-level dielectric layer **70**, and may be lithographically patterned to form an opening over the area of the drain-side contact via structure **74**. The drain-side contact via structure **74** may be vertically recessed to form a recess cavity **79** over a remaining portion of the drain-side contact via structure **74**, which is herein referred to as a lower drain-side contact via structure **74A**. The depth of the recess cavity **79** may be in a range from 10% to 90%, such as from 25% to 75%, of the height of the drain-side contact via structure **74** as formed at the processing steps of FIG. **9A**, although lesser and greater percentages may also be used. The photoresist layer **59** may be subsequently removed, for example, by ashing.

(110) Referring to FIG. **9C**, an antifuse dielectric layer **60** may be formed on the top surface of the lower drain-side contact via structure **74A** and on the sidewalls of the recess cavity **79** by depositing and patterning a dielectric material layer. The antifuse dielectric layer **60** may include any material that may be used for the antifuse dielectric layer **60** in any of the previously disclosed exemplary structures above.

(111) Referring to FIG. **9D**, a first-line-level dielectric layer **80** may be formed over the contact-level dielectric layer **70**. Line cavities may be formed in the first-line-level dielectric layer **80**, for example, by application and patterning of a photoresist layer (not shown) over the first-line-level dielectric layer **80** and by transferring the pattern in the photoresist layer through the first-line-level dielectric layer **80** by an anisotropic etch process. The anisotropic etch process may remove the portion of the dielectric material layer of the first-line-level dielectric layer **80** that fills a volume that is laterally surrounded by sidewalls of the antifuse dielectric layer **60**. A recessed top surface and inner sidewalls of the antifuse dielectric layer **60** may be physically exposed at the bottom of each cavity that is laterally surrounded by the antifuse dielectric layer **60**.

(112) At least one conductive material (such as a metallic barrier liner and a metallic fill material) may be deposited in the line cavities in the first-line-level dielectric layer **80** and in the cavity laterally surrounded by the antifuse dielectric layer **60** to form various metal line structures, which include a first-line-level source-side line structure **82** contacting the source-side contact via structure **72**, a first-line-level drain-side line structure **84** contacting the recessed horizontal surface

and the inner sidewall of the antifuse dielectric layer **60**, and a first-line-level gate connection line structure (not illustrated) contacting the gate contact via structure. The first-line-level drain-side line structure **84** includes a downward-protruding metal via portion that fills a cavity that is laterally surrounded by the antifuse dielectric layer **60**. The downward-protruding metal via portion of the first-line-level drain-side line structure **84** is a metal via portion, which is also referred to as an upper contact-level metal via structure **74B**.

(113) Referring to FIG. **10A**, a first embodiment of a tenth exemplary structure for forming a one time programmable memory device may be derived from the fifth exemplary structure of FIG. **5A** by forming a combination of a lower first-via-level metal via structure **94A**, an antifuse dielectric layer **60**, and an upper first-via-level metal via structure **94B** within a first-via-level dielectric layer **90** that includes a vertical stack of a lower first-via-level dielectric layer **90A** and an upper first-via-level dielectric layer **90B**.

(114) Referring to FIG. **10B**, a second embodiment of the tenth exemplary structure for forming a one time programmable memory device may be derived from the ninth exemplary structure by forming a combination of a lower first-via-level metal via structure **94A**, an antifuse dielectric layer **60**, and a second-line-level metal line structure **104** including a downward-protruding metal via portion that fills a recess cavity that is laterally surrounded by the antifuse dielectric layer **60**. The downward-protruding metal via portion of the second-line-level metal line structure **104** is herein referred to as an upper first-via-level metal via structure **94B**.

(115) Referring to FIG. **11A**, a first embodiment of an eleventh exemplary structure for forming a one time programmable memory device may be derived from the first embodiment of the tenth exemplary structure by forming a combination of a lower N-th-via-level metal via structure **134A**, an antifuse dielectric layer **60**, and an upper N-th-via-level metal via structure **134B** within an N-th-via-level dielectric layer **130** that includes a vertical stack of a lower N-th-via-level dielectric layer **130A** and an upper N-th-via-level dielectric layer **130B**. The processing steps of the eighth embodiment may be performed mutatis mutandis at the level of the N-th-via-level dielectric layer **130** to form the first embodiment of the eleventh exemplary structure. N may be a positive integer greater than 1.

(116) Referring to FIG. **11B**, a second embodiment of the eleventh exemplary structure for forming a one time programmable memory device may be derived from the second embodiment of the tenth exemplary structure by forming a combination of a lower N-th-via-level metal via structure **13A**, an antifuse dielectric layer **60**, and an (N+1)-th-line-level metal line structure **144** including a downward-protruding metal via portion that fills a recess cavity that is laterally surrounded by the antifuse dielectric layer **60**. The downward-protruding metal via portion of the (N+1)-th-line-level metal line structure **144** is herein referred to as an upper N-th-via-level metal via structure **134B**. N may be a positive integer greater than 1.

(117) Referring collectively to FIGS. **8A-11B**, a one time programmable memory device may be provided by: forming a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** on a substrate **8**; and by forming an antifuse structure {(74A, **60**, 74B), (94A, **60**, 94B), (134A, **60**, 134B)} including a first node (74A, 94A, 134A), an antifuse dielectric layer **60**, and a second node (74B, 94B, 134B) on, or over, the antifuse dielectric layer **60**, wherein one, or both, of the first node (74A, 94A, 134A) and the second node (74B, 94B, 134B) comprise a metal via structure (74A, 94A, 134A, 74B, 94B, 134B) formed within a via cavity extending through an interlayer dielectric material layer (70, 90, 130) that overlies the field effect transistor.

(118) In some embodiment, a recess cavity may be formed by vertically recessing a metal via structure (74, 94, 134). The antifuse dielectric layer **60** may be formed on the recessed top surface of the metal via structure (such as the lower drain-side contact via structure 74A, the lower first-via-level metal via structure 94A, or the lower N-th-via-level metal via structure 134A). Another metal via structure (such as the upper drain-side contact via structure 74B, the upper first-via-level

metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **8C**, **10A**, or **11A**) or a metal via portion (such as the upper drain-side contact via structure **74B**, the upper first-via-level metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **9D**, **10B**, or **11B**) of a metallic structure that includes a metal line structure (such as a first-line-level drain-side line structure **84**, a second-line-level metal line structure **104**, or an (N+1)-th-line-level metal line structure **144** in FIG. **9D**, **10B**, or **11B**) in the recess cavity.

(119) As such, the metal-insulator-metal (MIM) antifuse structure may include: a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** and located on a substrate **8**; and a first node (**74A**, **94A**, **134A**) electrically connected to the drain region **34**, a second node (**74B**, **94B**, **134B**) that is vertically spaced from the first node (**74A**, **94A**, **134A**), and an antifuse dielectric layer **60** located between the first node (**74A**, **94A**, **134A**) and the second node (**74B**, **94B**, **134B**), wherein one, or both, of the first node (**74A**, **94A**, **134A**) and the second node (**74B**, **94B**, **134B**) comprises a metal via structure (**74A**, **94A**, **134A**, **74B**, **94B**, **134B**) that is laterally surrounded by an interlayer dielectric material layer (**70**, **90**, **130**) that overlies the substrate **8**. Another of the first node (**74A**, **94A**, **134A**) and the second node (**74B**, **94B**, **134B**) comprises another metal via structure (such as the upper drain-side contact via structure **74B**, the upper first-via-level metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **8C**, **10A**, or **11A**) or a metal via portion (such as the upper drain-side contact via structure **74B**, the upper first-via-level metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **9D**, **10B**, or **11B**) of a metallic structure that includes a metal line structure (such as a first-line-level drain-side line structure **84**, a second-line-level metal line structure **104**, or an (N+1)-th-line-level metal line structure **144** in FIG. **9D**, **10B**, or **11B**).

(120) Referring to FIG. **12A**, a circuit schematic of an unprogrammed discrete OTP memory device according to an embodiment of the present disclosure is illustrated. The source region **32** may be electrically connected to a source line SL, which may be electrically biased at 0 V during operation. The second node of the antifuse structure is connected to a bit line BL. The gate electrode **52** may be electrically connected to a word line WLR, which has a gate resistance $R_{\text{sub.WLR}}$. The antifuse structure functions as a capacitor, through which direct current does not flow. The unprogrammed state of the antifuse may be logically equivalent to a “0” state.

(121) Referring to FIG. **12B**, a circuit schematic of a programmed discrete OTP memory device according to an embodiment of the present disclosure is illustrated. The source region **32** may be electrically connected to a source line SL, which may be electrically biased at 0 V during operation. The gate electrode **52** may be electrically connected to a word line WLR, which has a gate resistance $R_{\text{sub.WLR}}$. The programmed antifuse structure functions as a resistor, through which direct current flows when the bit line BL is biased at a read voltage. The unprogrammed state of the antifuse may be logically equivalent to a “1” state.

(122) Referring to FIG. **13**, a two-dimensional array of OTP memory devices according to an embodiment of the present disclosure is illustrated, which may be provided by forming multiple instances of any configuration of the OTP memory device of the present disclosure in a two-dimensional array configuration. Multiple source lines SL_i , multiple word lines WLR_j , and multiple bit lines BL_k may be formed. The indices i , j , and k may be non-negative integers beginning with 0.

(123) Referring to FIG. **14**, a circuit schematic of a 32×2 bit cell block is illustrated, in which each pair of OTP memory devices shares a respective source line SL_i according to an embodiment of the present disclosure. Two word lines and two bit lines may be shared by a respective set of 32 memory cells.

(124) Referring to FIG. **15**, various peripheral devices may be provided for the 32×2 bit cell block illustrated in FIG. **14**. For example, a bit decoder, a source-side power supply circuit, and a bit-line-side power supply transistor (such as CT0 and CT1) may be used.

(125) While FIGS. **13-15** illustrate exemplary memory arrays that may be formed using a two-

dimensional array of OTP memory devices of the present disclosure, it is understood that an array of OTP memory devices of the present disclosure may be formed in any array configuration known in the art.

(126) Referring to FIG. **16**, a first flow chart **1600** illustrates a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure. Referring to step **1610**, a field effect transistor including a source region **32**, a drain region **34** that comprises a first node of an antifuse structure, a gate dielectric **50**, and a gate electrode **52** may be formed on a substrate **8**. Referring to step **1620**, an antifuse dielectric layer **60** may be formed on the drain region **34**. Referring to step **1630**, a second node including a metallic material portion (such as a drain-side metallic material portion **44**) may be formed on the antifuse dielectric layer **60**. The embodiments of the first exemplary structure of FIGS. **1D-1G** may be formed by this method.

(127) Referring to FIG. **17**, a second flow chart **1700** illustrates a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure. Referring to step **1710**, a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** may be formed on a substrate **8**. Referring to step **1720**, a drain-side metallic material portion **44** comprising a first node of an antifuse structure may be formed on the drain region **34**. Referring to step **1730**, an antifuse dielectric layer **60** may be formed on the drain-side metallic material portion **44**. Referring to step **1740**, an interlayer dielectric material layer (such as a contact-level dielectric layer **70**) and a via cavity therethrough may be formed over the antifuse dielectric layer **60**. Referring to step **1750**, a second node including a metal via structure (such as a drain-side contact via structure **74**) may be formed within the via cavity. The second exemplary structure of FIGS. **2D-2G** may be formed by this method.

(128) Referring to FIG. **18**, a third flow chart **1800** illustrates a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure. Referring to step **1810**, a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** may be formed on a substrate **8**. Referring to step **1820**, a first node including a metal line structure (**84**, **124**) that is formed in a first interlayer dielectric material layer (**80**, **120**) and electrically connected to the drain region **34** may be formed. Referring to step **1830**, an antifuse dielectric layer **60** may be formed on the first node. Referring to step **1840**, a second interlayer dielectric material layer (**90**, **130**) and a via cavity therethrough may be formed over the antifuse dielectric layer **60**. Referring to step **1850**, a second node including a metal via structure (**94**, **134**) may be formed within the via cavity. The fourth exemplary structures of FIGS. **4A-4D** and the sixth exemplary structure of FIG. **6** may be formed by this method.

(129) Referring to FIG. **19**, a fourth flow chart **1900** illustrates a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure. Referring to step **1910**, a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** may be formed on a substrate **8**. Referring to step **1920**, a first node including a metal via structure (**74**, **94**, **134**) that is formed in a first interlayer dielectric material layer (**70**, **90**, **130**) and electrically connected to the drain region **34** is formed. Referring to step **1930**, an antifuse dielectric layer **60** may be formed on the first node. Referring to step **1940**, a second interlayer dielectric material layer (**80**, **100**, **140**) and a line cavity therethrough may be formed over the antifuse dielectric layer **60**. Referring to step **1950**, a second node including a metal line structure (**84**, **104**, **144**) may be formed within the via cavity. The third exemplary structures of FIGS. **3A-3E**, the fifth exemplary structures of FIGS. **5A** and **5B**, and the seventh exemplary structures of FIGS. **7A** and **7B** may be formed by this method.

(130) Referring to FIG. **20**, a fifth flow chart **2000** illustrates a set of processing steps for forming an OTP memory device according to an embodiment of the present disclosure. Referring to step **2010**, a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** may be formed on a substrate **8**. Referring to step **2020**, an interlayer dielectric material layer (**70**, **90**, **130**) and a via cavity therethrough may be formed over the field

effect transistor. Referring to step **2030**, a first node including a metal via structure (**74A**, **94A**, **134A**) and electrically connected to the drain region **34** may be formed in the via cavity. Referring to step **2040**, an antifuse dielectric layer **60** may be formed on the first node. Referring to step **2050**, a second node including another metal via structure (such as the upper drain-side contact via structure **74B**, the upper first-via-level metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **8C**, **10A**, or **11A**) or a metal via portion (such as the upper drain-side contact via structure **74B**, the upper first-via-level metal via structure **94B**, or the upper N-th-via-level metal via structure **134B** in FIG. **9D**, **10B**, or **11B**) of a metallic structure including a metal line structure (such as a first-line-level drain-side line structure **84**, a second-line-level metal line structure **104**, or an (N+1)-th-line-level metal line structure **144** in FIG. **9D**, **10B**, or **11B**) over the antifuse dielectric layer. The eighth exemplary structure of FIG. **8C**, the ninth exemplary structure of FIG. **9D**, the tenth exemplary structures of FIGS. **10A** and **10B**, and the eleventh exemplary structures of FIGS. **11A** and **11B** may be formed by this method.

(131) Referring to FIG. **21**, a sixth flow chart **2100** illustrates a set of processing steps for forming an OTP memory device, which may be used to form any of the OTP memory devices of the present disclosure. Referring to step **2110**, a field effect transistor including a source region **32**, a drain region **34**, a gate dielectric **50**, and a gate electrode **52** is formed on a substrate **8**. Referring to step **2120**, an antifuse dielectric layer **60** may be deposited on the drain region **34** or a conductive material portion (**44**, **84**, **124**, **74**, **94**, **134**, **74A**, **94A**, **134A**) that is formed over the drain region **34** and electrically connected to the drain region **34**. The drain region **34** or the conductive material portion (**44**, **84**, **124**, **74**, **94**, **134**, **74A**, **94A**, **134A**) comprises a first node of an antifuse structure. Referring to step **2130**, a second node (**44**, **84**, **104**, **144**, **74**, **94**, **134**, **74B**, **94B**, **134B**) of the antifuse structure is formed directly on the antifuse dielectric layer **60**. The first node comprises the drain region **34**, or one of the first node (**34**, **44**, **84**, **124**, **74**, **94**, **134**, **74A**, **94A**, **134A**) and the second node (**44**, **84**, **104**, **144**, **74**, **94**, **134**, **74B**, **94B**, **134B**) comprises a metal via structure (**74**, **94**, **134**, **74A**, **94A**, **134A**, **74B**, **94B**, **134B**) formed within a via cavity extending through an interlayer dielectric material layer (**70**, **90**, **130**) that overlies the field effect transistor.

(132) The various embodiments of the present disclosure provide an OTP memory device including an antifuse structure that is formed in middle-end-of-line (MEOL) level or back-end-of-line (BEOL) level. Selection of an OTP memory device within an array of OTP memory devices may be effected by a respective field effect transistor. Because the antifuse structure is formed in the MEOL level or in the BEOL level, the front-end-of-line (FEOL) processes are not affected by integration of the OTP memory device into a semiconductor processing sequence. Thus, gate resistance effect may be avoided, an lower programming voltages may be used, which may be in a range from 4 V to 30 V. Thus, program disturb immunity among adjacent OTP memory devices may be reduced, and read voltage may be lowered and read process window may be expanded. The OTP memory device of the present disclosure may thus facilitate scaling of the memory device through reduction of device dimensions. The smallest bit-cell size and better read window may be provided.

(133) According to an embodiment of the present disclosure, an one time programmable (OTP) memory device may be provided, where the OTP memory device includes a field effect transistor. The field effect transistor including a source region, a drain region, a gate dielectric, and a gate electrode and located on a substrate. The OTP memory device further including a semiconductor-insulator-metal (SIM) antifuse structure, where the SIM antifuse structure includes the drain region that constitutes a first node, a drain-side metallic material portion that constitutes a second node that is spaced from the first node, and an antifuse dielectric layer located between the first node and the second node.

(134) According to another embodiment of the present disclosure, an one time programmable (OTP) memory device may be provided, where the OTP memory device includes a field effect transistor. The field effect transistor including a source region, a drain region, a gate dielectric, and a gate electrode and

located on a substrate. The OTP memory device further including a metal-insulator-metal (MIM) antifuse structure, where the MIM antifuse structure includes a first node electrically connected to the drain region, a second node that is vertically spaced from the first node, and an antifuse dielectric layer located between the first node and the second node, wherein one of the first node and the second node comprises a metal via structure that is laterally surrounded by an interlayer dielectric material layer that overlies the substrate.

(135) According to another embodiment of the present disclosure, a method of forming a one time programmable memory device is provided, wherein the method includes the operations of: forming a field effect transistor including a source region, a drain region, a gate dielectric, and a gate electrode on a substrate; and forming an antifuse structure including a first node, an antifuse dielectric layer, and a second node on, or over, the antifuse dielectric layer, wherein one of the first node and the second node comprises the drain region or a metal via structure formed within a via cavity extending through an interlayer dielectric material layer that overlies the field effect transistor.

(136) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A one time programmable (OTP) memory device comprising: a field effect transistor including a source region, a drain region, a gate dielectric, and a gate electrode and located on a substrate; a semiconductor-insulator-metal (SIM) antifuse structure including the drain region that constitutes a first node, a drain-side metallic material portion that constitutes a second node that is spaced from the first node, and an antifuse dielectric layer located between the first node and the second node, wherein a periphery of a top surface of the antifuse dielectric layer is laterally offset relative to a periphery of a bottom surface of the drain-side metallic material portion; and an etch stop dielectric layer contacting a top surface of the drain region and having an opening therein, wherein: the opening has a lesser area than an area of the top surface of the drain region; the antifuse dielectric layer comprises a portion that is located within the opening; a bottom surface of the antifuse dielectric layer is located within a first horizontal plane including a bottom surface of the etch stop dielectric layer; and a top surface of the antifuse dielectric layer is located within a second horizontal plane including a top surface of the etch stop dielectric layer.
2. The OTP memory device of claim 1, wherein: the antifuse dielectric layer is located entirely within the opening in the etch stop dielectric layer; and the antifuse dielectric layer comprises a dielectric material having a lower dielectric breakdown electrical field strength than the etch stop dielectric layer.
3. The OTP memory device of claim 1, further comprising: a drain-side contact via structure contacting a top surface of the drain-side metallic material portion; and an interlayer dielectric material layer laterally surrounding the drain-side metallic material portion and the drain-side contact via structure.
4. The OTP memory device of claim 3, wherein: the drain-side metallic material portion has a greater lateral extent than the drain-side contact via structure; and the interlayer dielectric material layer laterally surrounds the gate electrode; and the drain-side contact via structure has a top surface within a same horizontal plane as a top surface of the interlayer dielectric material layer.

5. The OTP memory device of claim 1, wherein a first edge of a top surface of the etch stop dielectric layer coincides with a first edge of the bottom surface of the drain-side metallic material portion.
6. The OTP memory device of claim 5, wherein the field effect transistor comprises a dielectric gate spacer laterally surrounding the gate dielectric and the gate electrode, wherein the first edge of the top surface of the etch stop dielectric layer is in direct contact with an outer sidewall of the dielectric gate spacer.
7. The OTP memory device of claim 1, further comprising a shallow trench isolation structure laterally surrounding the source region and the drain region, wherein the shallow trench isolation structure contacts the etch stop dielectric layer.
8. The OTP memory device of claim 7, wherein the antifuse dielectric layer is not in direct contact with the shallow trench isolation structure.
9. The OTP memory device of claim 1, further comprising a source-side metallic material portion in direct contact with the source region and comprising a first portion of a metallic material selected from at least one conductive metallic nitride material and a metal semiconductor alloy.
10. A one time programmable (OTP) memory device comprising: a field effect transistor including a source region, a drain region, a gate dielectric, a gate electrode, and a dielectric gate spacer and located on a substrate; a source-side metallic material portion in direct contact with the source region and comprising a first portion of a metallic material; a semiconductor-insulator-metal (SIM) antifuse structure including the drain region that constitutes a first node, a drain-side metallic material portion that constitutes a second node that is spaced from the first node and comprising a second portion of said metallic material, and a dielectric structure comprising an antifuse dielectric layer and located between the first node and the second node and contacting a horizontal top surface of the drain region and contacting a horizontal bottom surface of the second portion of said metallic material, wherein a sidewall of the dielectric structure is in direct contact with a first portion of an outer sidewall of the dielectric gate spacer; and an etch stop dielectric layer contacting a top surface of the drain region and having an opening therein, wherein: the opening has a lesser area than an area of the top surface of the drain region; the antifuse dielectric layer comprises a portion that is located within the opening; a bottom surface of the antifuse dielectric layer is located within a first horizontal plane including a bottom surface of the etch stop dielectric layer; and a top surface of the antifuse dielectric layer is located within a second horizontal plane including a top surface of the etch stop dielectric layer.
11. The OTP memory device of claim 10, wherein the drain-side metallic material portion is in direct contact with a second portion of the outer sidewall of the dielectric gate spacer.
12. The OTP memory device of claim 10, wherein: the etch stop dielectric layer is in contact with the first portion of the outer sidewall of the dielectric gate spacer; and the antifuse dielectric layer is not in contact with the dielectric gate spacer.
13. The OTP memory device of claim 10, further comprising a shallow trench isolation structure laterally surrounding the source region and the drain region, wherein: the etch stop dielectric layer is in contact with the shallow trench isolation structure; and the antifuse dielectric layer is not in contact with the shallow trench isolation structure.
14. The OTP memory device of claim 10, wherein a first edge of a top surface of the etch stop dielectric layer coincides with a first edge of the bottom surface of the drain-side metallic material portion.
15. The OTP memory device of claim 14, wherein the dielectric gate spacer is laterally surrounding the gate dielectric and the gate electrode, wherein the first edge of the top surface of the etch stop dielectric layer is in direct contact with an outer sidewall of the dielectric gate spacer.
16. A one time programmable (OTP) memory device comprising: a field effect transistor including a source region, a drain region, a gate dielectric, and a gate electrode and located on a substrate; a source-side metallic material portion in direct contact with the source region and comprising a first

portion of a metallic material; a semiconductor-insulator-metal (SIM) antifuse structure including the drain region that constitutes a first node, a drain-side metallic material portion that constitutes a second node that is spaced from the first node and comprising a second portion of said metallic material, and an antifuse dielectric layer located between the first node and the second node and contacting a horizontal top surface of the drain region and contacting a horizontal bottom surface of second portion of said metallic material; and an etch stop dielectric layer contacting a top surface of the drain region and having an opening therein, wherein: the opening has a lesser area than an area of the top surface of the drain region; the antifuse dielectric layer comprises a portion that is located within the opening; a bottom surface of the antifuse dielectric layer is located within a first horizontal plane including a bottom surface of the etch stop dielectric layer; a top surface of the antifuse dielectric layer is located within a second horizontal plane including a top surface of the etch stop dielectric layer; and the source-side metallic material portion has a same thickness as the drain-side metallic material portion.

17. The OTP memory device of claim 16, further comprising a dielectric gate spacer laterally surrounding the gate dielectric and the gate electrode, wherein: the etch stop dielectric layer is in contact with the first portion of the outer sidewall of the dielectric gate spacer; and the antifuse dielectric layer is not in contact with the dielectric gate spacer.

18. The OTP memory device of claim 16, further comprising a shallow trench isolation structure laterally surrounding the source region and the drain region, wherein: the etch stop dielectric layer is in contact with the shallow trench isolation structure; and the antifuse dielectric layer is not in contact with the shallow trench isolation structure.

19. The OTP memory device of claim 16, further comprising a shallow trench isolation structure laterally surrounding the source region and the drain region, wherein the shallow trench isolation structure contacts the etch stop dielectric layer.

20. The OTP memory device of claim 19, wherein the antifuse dielectric layer is not in direct contact with the shallow trench isolation structure.
