

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12411412
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Murphy; Michael et al.

Patterning semiconductor features

Abstract

In certain embodiments, a method includes forming, by photolithography on a semiconductor wafer, first patterned features (PFs) including first photoresist structures (PRs) having a first width and first recesses having a second width less than the first width and greater than a target width; forming, via anti-spacer patterning processing, second PFs including second PRs having a third width less than the first width, first overcoat structures (OCSs) of the second width interspersed between second PRs, and second recesses having a fourth width less than the target width; and forming, via acid diffusion processing, third PFs including third PRs having a fifth width, second OCSs of the target width interspersed between third PRs, and third recesses defined by third PRs and second OCSs and having a sixth width greater than the fourth width, portions of first OCSs having been selectively removed using the acid diffusion processing to form second OCSs.

Inventors: Murphy; Michael (Albany, NY), Cutler; Charlotte (Albany, NY), Conklin; David (Saratoga Springs, NY)

Applicant: Tokyo Electron Limited (Tokyo, JP)

Family ID: 91080973

Assignee: Toyko Electron Limited (Tokyo, JP)

Appl. No.: 17/992522

Filed: November 22, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20240168384 A1	May. 23, 2024

Publication Classification

Int. Cl.: G03F7/16 (20060101); **G03F7/00** (20060101); **G03F7/30** (20060101); **G03F7/38** (20060101); **G03F7/40** (20060101)

U.S. Cl.:

CPC G03F7/168 (20130101); **G03F7/0035** (20130101); **G03F7/30** (20130101); **G03F7/38** (20130101); **G03F7/40** (20130101);

Field of Classification Search

CPC: G03F (7/11); G03F (7/0035); G03F (7/38); G03F (7/40); G03F (7/30)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8900797	12/2013	Nakasugi et al.	N/A	N/A
2007/0077524	12/2006	Koh	257/E21.026	H01L 21/0338
2009/0142711	12/2008	Jung et al.	N/A	N/A
2010/0130016	12/2009	DeVilliers	438/703	H01L 21/32139
2011/0027993	12/2010	Moon	438/689	G03F 7/40
2013/0171574	12/2012	Xu	N/A	N/A
2016/0181115	12/2015	deVilliers	438/695	H01L 21/32139

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2015157416	12/2014	WO	N/A

OTHER PUBLICATIONS

PCT International Search Report and Written Opinion of the International Searching Authority, PCT/US2023/037212, dated Mar. 12, 2024, 9 pages. cited by applicant

Bencher et al., “22nm Half-Pitch Patterning by CVD Spacer Self Alignment Double Patterning (SADP),” Proceedings of SPIE—The International Society for Optical Engineering, Proc. of SPIE vol. 6924, Mar. 2008, 8 pages. cited by applicant

Hyatt et al., “Anti-spacer double patterning,” SPIE Advanced Lithography, Proc. of SPIE vol. 905, Mar. 27, 2014, SPIEDigitalLibrary.org/conference-proceedings-of-spie, San Jose, California, United States, 10 pages. cited by applicant

Nakamura et al., “Process feasibility investigation of freezing free litho-litho-etch process for below 32nm hp,” Advances in Resist Materials and Processing Technology XXVII, Proc. of SPIE vol. 7639, SPIE Advanced Lithography, Mar. 25, 2010, SPIEDigitalLibrary.org/conference-proceedings-of-spie, San Jose, California, United States, 9 pages. cited by applicant

Nakamura et al., “Process Feasibility Investigation of Freezing Free Process,” Journal of Photopolymer Science and Technology, vol. 22, No. 5, Jun. 8, 2009, 6 pages. cited by applicant

Sakamoto et al., “Bottom-Anti-Reflective coatings (BARC) for LFLE Double patterning process,” Proceedings of SPIE—The International Society for Optical Engineering, Proc. of SPIE vol. 7520, Dec. 2009, 11 pages. cited by applicant

Primary Examiner: Raymond; Brittany L

Attorney, Agent or Firm: Slater Matsil, LLP

Background/Summary

TECHNICAL FIELD

(1) This disclosure relates generally to semiconductor fabrication, and, in particular embodiments,

to patterning semiconductor features.

BACKGROUND

(2) Semiconductor devices typically are fabricated by sequentially depositing insulating or dielectric layers, conductive layers, and other layers of material over a semiconductor substrate, and patterning the layers using lithography to form circuit components and elements on the substrate. The semiconductor industry continues to increase the density of electronic components (e.g., transistors, diodes, resistors, capacitors, etc.) by continual reductions in minimum feature size, allowing more components to be integrated into a particular area.

SUMMARY

(3) In certain embodiments, a method includes depositing a first overcoat film on a semiconductor wafer that includes first patterned features of a photoresist layer, the first patterned features include first photoresist structures and first recesses defined by the first photoresist structures. The first overcoat film fills the first recesses and covers the first photoresist structures. The first recesses have first widths that are greater than a target width. The method includes baking the semiconductor wafer to form soluble portions of the first photoresist structures, selectively removing the first overcoat film, and depositing a second overcoat film that fills the first recesses and covers the first photoresist structures. The method includes developing the semiconductor wafer to remove portions of the second overcoat film to reveal and remove the soluble portions of the first photoresist structures to define second patterned features that include second photoresist structures, first overcoat structures interspersed between the second photoresist structures, and second recesses defined by the second photoresist structures and the first overcoat structures. The method includes executing a solubility-changing process to cause the first overcoat structures to become insoluble for development, depositing a third overcoat film that fills the second recesses and covers the second photoresist structures and the first overcoat structures, and baking the semiconductor wafer to form soluble portions of the first overcoat structures. The method includes developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures to define third patterned features that include third photoresist structures, second overcoat structures interspersed between the third photoresist structures, and third recesses defined by the second overcoat structures and the third photoresist structures. The second overcoat structures have the target width.

(4) In certain embodiments, a method includes forming, on a semiconductor wafer by photolithography, first photoresist structures having a first width and first recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width. The method includes depositing a first overcoat film; forming, using the first overcoat film, soluble portions of the first photoresist structures; selectively removing the first overcoat film; and depositing a second overcoat film. The method includes removing portions of the second overcoat film and the soluble portions of the first photoresist structures to define second photoresist structures, first overcoat structures of the second overcoat film, and second recesses in regions previously occupied by the soluble portions of the first photoresist structures. The second photoresist structures have a third width less than the first width, the first overcoat structures have the second width, and the second recesses have a fourth width less than the target width. The method includes modifying the first overcoat structures to become insoluble for development; depositing a third overcoat film; forming, using the third overcoat film, soluble portions of the first overcoat structures; and selectively removing the third overcoat film and the soluble portions of the first overcoat structures to define third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having a sixth width equal to the target width, and third recesses defined by the third photoresist structures and the second overcoat structures and having a seventh width greater than the fourth width.

(5) In certain embodiments, a method includes forming, by photolithography on a semiconductor wafer, first patterned features including first photoresist structures having a first width and first

recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width. The method includes forming, using an anti-spacer patterning process, second patterned features including second photoresist structures having a third width less than the first width, first overcoat structures interspersed between the second photoresist structures and having the second width, and second recesses defined by the second photoresist structures and the first overcoat structures and having a fourth width less than the target width. The method includes forming, using an acid diffusion process, third patterned features that include third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having the target width, and third recesses defined by the third photoresist structures and the second overcoat structures and having a sixth width greater than the fourth width, portions of the first overcoat structures having been selectively removed using the acid diffusion process to form the second overcoat structures.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) For a more complete understanding of the present disclosure, and the advantages thereof, reference is now made to the following descriptions taken in conjunction with the accompanying drawings, in which:
- (2) FIGS. 1A-1K illustrate cross-sectional and plan views of an example semiconductor workpiece during an example patterning process, according to certain embodiments;
- (3) FIG. 2 illustrates a plan view of an example semiconductor workpiece during an example patterning process (e.g., at a state illustrated in FIG. 1J), according to certain embodiments;
- (4) FIG. 3 illustrates an example method for patterning a semiconductor workpiece, according to certain embodiments;
- (5) FIG. 4 illustrates an example method for patterning a semiconductor workpiece, according to certain embodiments;
- (6) FIG. 5 illustrates an example method for patterning a semiconductor workpiece, according to certain embodiments;
- (7) FIG. 6 illustrates a block diagram of an example lithography system, according to certain embodiments; and
- (8) FIG. 7 illustrates an example liquid-based spin-on deposition system, according to certain embodiments.

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

- (9) As described above, as semiconductor devices have continued to shrink, the dimensions of features formed on a semiconductor substrate also have decreased while a density of those features within smaller areas has increased. With this reduction in feature size and increase in density, difficulties associated with patterning at or below photolithography limits has grown.
- (10) The minimum feature size (including patterned structures and recesses defined by those patterned structures) that may be directly achievable using a photolithography technology may be determined according to a photolithography technology used to pattern the features (e.g., in a photoresist layer that may be used to transfer the pattern to one or more underlying layers). For example, different photolithography technologies may use different wavelengths of radiation to deliver actinic radiation to a target layer (e.g., to a photoresist layer to be patterned using photolithography). The wavelength of radiation may affect the minimum feature size achievable during photolithography patterning. In general, the smaller the feature size that is attainable, the more advanced and expensive the lithography equipment for achieving that features size. For example, some newer technologies, such as extreme ultraviolet (EUV) lithography, are able to directly achieve relatively small feature sizes, approaching a 13 nanometer (nm) half pitch using

EUV 13.5 nm wavelength at 0.33 numerical aperture (NA). However, these newer technologies may suffer certain drawbacks, including expense.

(11) Some older lithography technologies, such as 193 nm dry photolithography, 193 nm immersion photolithography, i-line photolithography, and others, remain commonly used and may be used in combination with other processes to achieve smaller features sizes than may be achieved directly using the older photolithography technology. That is, certain techniques may be used to allow certain feature sizes to be achieved that go beyond the feature sizes that may be directly achieved using a particular lithography technology. Such smaller features may be referred to as sub-resolution features.

(12) Various multi-patterning technologies may be used to attempt to meet these demands, including self-aligned double-patterning (SADP), litho-etch-litho-etch (LELE), litho-freeze-litho-etch (LFLE), and self-aligned block (SAB). Self-aligned patterning schemes such as SADP may facilitate forming sub-resolution features at a fraction of the original pitch while minimizing edge placement error. SADP processes, however, may rely on depositing and etching inorganic spacers such as amorphous silicon or silicon nitride to resolve final features. Such processes may reduce throughput while increasing cost and complexity of integration to maximize pattern fidelity and etch selectivity.

(13) Another example SADP technique that may be used to achieve sub-resolution features is an anti-spacer patterning process that may use spin-on organic films and diffusion of reactive species (e.g., acid) relative to a photoresist structure (e.g., a mandrel) to form sub-resolution trenches with relatively high throughput and low cost. Anti-spacer process flows use the reactive nature of photoresists to be either the diffuser or reactant of a reactive species across an overcoat-photoresist boundary in which the diffusion length and reaction within said volume may determine the critical dimension (CD) of a patterned feature.

(14) In an example anti-spacer flow, a reactive species may diffuse from a first overcoat into a patterned photoresist structure (e.g., mandrel) causing deprotection of the patterned photoresist feature to a specified depth. The first overcoat may be selectively removed and replaced with a second overcoat. The second overcoat may be designed to controllably recess during a development process to expose the deprotected patterned photoresist feature and resolve narrow trenches with CDs controlled by the depth of diffusion that occurred with the first overcoat. The spin-on nature of the overcoats and relatively short bake times for diffusion of the reactive species into the patterned photoresist structures may provide an overall patterning process with high throughput and low relative cost. However, such a patterning process that involves diffusion of a reactive species into a photoresist structure may be limited with respect to the final pitch of the narrow trench features.

(15) Among the characteristics of a pattern formed using a lithographic patterning process is feature pitch. Feature pitch may refer to the length of a repeat pattern of patterned features. As just one example, if the patterned features include a line-space-line-space pattern, a pitch may include a combination of the widths of a line and an adjacent space. Along with other pattern characteristics, the feature pitch indicates the density of features that can be achieved using the patterning process, and in general, a smaller pitch is desired as a smaller pitch may allow more features to be formed in a smaller area. Furthermore, in some implementations, having a consistent, repeatable pitch may be appropriate. Such a pitch may include a feature pitch ratio of, for example, 1:1:1:1 for a line-space-line-space pattern.

(16) Using the above-described anti-spacer flow, the feature pitch may be limited by the narrowest recess (e.g., trench) that may be lithographically formed between dense lines. Taking an example in which a 193 nm dry photolithography technology is used to pattern a photoresist layer on a semiconductor wafer, and with a goal to form a 45 nm 1:1 dense line-space pattern, 193 nm dry photolithography exposure tools may be unable to directly pattern a photoresist pattern of 135 nm line and 45 nm trench to form a 45 nm 1:1 line-space pattern. In other words, a 193 nm dry

photolithography exposure may be unable to form 3:1 line-space ratio of 135 nm:45 nm that would be appropriate to achieve a final 45 nm 1:1 line-space target. Instead, the 193 nm dry photolithography tool might more realistically be used to pattern at a 180 nm pitch in which a 110 nm line and a 70 nm trench are formed. However, using the above-described anti-spacer process to reduce the 70 nm trench to a 45 nm anti-spacer trench may result in a non-uniform asymmetrical final pitch of, potentially, 70 nm:45 nm:20 nm:45 nm line-space-line-space pattern, which may be undesirable for particular applications, many of which target pitch patterns approaching or achieving a 1:1:1:1 pitch pattern.

(17) Certain embodiments of this disclosure provide techniques for achieving sub-resolution features while reducing or minimizing feature pitch ratio. In certain embodiments, a feature pitch ratio of 1:1:1:1 for a line-space-line-space feature pattern may be achieved. Certain embodiments accomplish this by widening the anti-spacer (trench/recess) CD post-anti-spacer reveal to achieve, potentially, a more similar or even same CD across the lines and spaces.

(18) For example, certain embodiments include forming, using photolithography, first patterned features on a semiconductor wafer. The first patterned features include first photoresist structures (e.g., lines) having first widths and first recesses (e.g., trenches/spaces) defined by the first photoresist structures and having second widths. Due at least in part to limitations of the photolithography technology, the second widths are greater than a target width. Additionally, a pitch ratio is greater than a target pitch ratio.

(19) Continuing, using an anti-spacer process, second patterned features are formed on the semiconductor wafer. The second patterned features include second photoresist structures (formed by solubilizing and removing, as part of the anti-spacer process, portions of the first photoresist structures), first overcoat structures formed in spaces where the first recesses were previously located, and second recesses formed in spaces where portions of the first photoresist structures were removed (the anti-spacers). While the second photoresist structures might or might not have a target width at this stage, the first overcoat structures may be wider than a target width and the second recesses may be narrower than a target width. Additionally, a pitch ratio is greater than a target pitch ratio.

(20) Continuing, using an acid diffusion process, third patterned features are formed on the semiconductor wafer. The third patterned features include third photoresist structures (which might or might not have the same width as the second photoresist structures), second overcoat structures formed by removing (via the acid diffusion process) portions of the first overcoat structures, and third recesses that have been widened due to the removal of portions of the first overcoat structures. In certain embodiments, at this stage, the third patterned features each have respective target widths, which might be the same target widths. Additionally, a pitch ratio may be a target pitch ratio, which in one example is a 1:1:1:1 line(third overcoat structure)-space(third recess)-line(second overcoat structure)-space(third recess) pitch ratio.

(21) FIGS. 1A-1K illustrate cross-sectional and plan views of an example semiconductor workpiece **100** during an example patterning process **102**, according to certain embodiments. In certain embodiments, some or all of patterning process **102** may be referred to as an anti-spacer process. In certain embodiments, patterning process **102** may be used to achieve sub-resolution features in an underlying layer of a semiconductor wafer. Furthermore, in certain embodiments, patterning process **102** may be used to reduce a lithographic pitch, potentially to a 1:1:1:1 line-space-line-space pitch ratio.

(22) Throughout the description of patterning process **102**, this disclosure describes an example in which patterning process **102** targets a line width of 45 nm, a recess (space) width of 45 nm, and a 1:1 feature pitch ratio (e.g., a 1:1:1:1 line-space-line-space pitch ratio). This disclosure, however, contemplates pursuing lines widths, recess widths, and pitch ratios of any suitable value, whether or not equal. For example, embodiments of this disclosure may provide an ability to form features that have a consistent pitch, but also may provide features that have a reduced pitch ratio even if

not equal. As another example, the particular line width and spacer width that may be achieved may depend on the particular lithography technology used initially to form patterned structures in a photoresist layer.

(23) Semiconductor workpiece **100** generically refers to any suitable semiconductor element being processed in accordance with embodiments of this disclosure. Semiconductor workpiece **100**, or portions thereof, also may be referred to as a semiconductor wafer (or just wafer), such as a silicon wafer. Semiconductor workpiece **100** includes a substrate **104**, an intermediate layer **106** positioned on substrate **104**, and patterned features **108** positioned on intermediate layer **106**.

(24) Substrate **104** may include any material portion or structure of a device, particularly a semiconductor or other electronics device, and may, for example, be a base substrate structure, such as a semiconductor wafer, reticle, or a layer on or overlying a base substrate structure such as a thin film. Thus, substrate **104** is not limited to any particular base structure, underlying layer or overlying layer, patterned or un-patterned, but rather, may include any such layer or base structure, and any combination of layers and/or base structures. Substrate **104** may be a bulk substrate such as a bulk silicon wafer, a silicon-on-insulator (SOI) wafer, or various other semiconductor substrates.

(25) In certain embodiments, substrate **104** may include silicon germanium, silicon carbide, gallium arsenide, gallium nitride, or other compound semiconductors. In certain embodiments, substrate **104** includes heterogeneous layers such as silicon germanium on silicon, gallium nitride on silicon, silicon carbon on silicon, as well layers of silicon on a silicon or SOI substrate. In certain embodiments, substrate **104** is patterned or embedded in other components of a semiconductor device.

(26) Intermediate layer **106** and patterned features **108** may be a photolithography stack. Intermediate layer **106** also may be referred to as an underlying layer, particularly in when described relative to patterned features **108** or the layer from which patterned features **108** are formed.

(27) Intermediate layer **106** represents any suitable combination of one or more layers, one or more of which are to be patterned using patterned features **108**. For example, intermediate layer **106** may include a hard mask layer, a planarization layer, an amorphous carbon layer, a silicon carbide layer, a bottom anti-reflective coating, and/or any other layer, one or more of which may be used for a patterning process. Additionally or alternatively, intermediate layer **106** may include a stack of films. For example, intermediate layer **106** may include films of dielectric and/or conductive materials, such as oxide, silicon oxide, silicon nitride, silicon oxynitride, silicon carbide, titanium nitride, tantalum nitride, their alloys, and combinations thereof. For example, intermediate layer **106** can be a dielectric layer or alternating dielectric layers.

(28) Semiconductor workpiece **100** may be formed in any suitable manner, including using any suitable combination of wet and/or dry deposition and etch techniques. For example, semiconductor workpiece **100** may be deposited using any technique appropriate for the material to be deposited and the semiconductor feature being formed. Suitable deposition processes may include a spin-on coating process, a chemical vapor deposition (CVD) process, an atomic layer deposition (ALD) process, plasma deposition processes (e.g., a plasma-enhanced CVD (PECVD) process), and/or other layer deposition processes or combinations of processes.

(29) Patterned features **108** may include photoresist structures **109** and recesses **110** defined by photoresist structures **109**. Photoresist structures **109** may be formed of any suitable material and may be lines or other suitable types of semiconductor structures. In certain embodiments, photoresist structures **109** are formed of a photoresist material.

(30) Photoresist structures **109** may be formed from a photoresist layer that is deposited over intermediate layer **106**. The photoresist layer may include any suitable type of layer that may be used to form a masking layer for patterning intermediate layer **106**, and may be made of a suitable material for acting as a photoresist. The photoresist layer is a layer to be patterned by an exposure step, such as by using an exposure module, which may be referred to as a scanner or stepper, and

subsequent development step to form patterned features **108**. For example, the photoresist layer may include a light-sensitive material made of a polymer, a solvent, and a sensitizer. The polymer is designed to change its structure when exposed to actinic radiation. The solvent allows the material of the photoresist layer to be spun to form a thin layer on an underlying layer (e.g., intermediate layer **106**). The sensitizer (or inhibitor) controls the photoreaction in a polymer phase. (31) For example, the photoresist layer can be a chemically-amplified resist (CAR). As another example, the photoresist layer may be a metal-based resist material such as an organometallic material such as a metal oxide (MOx) photoresist. The photoresist material of the photoresist layer may be appropriate for the type of photolithography technology to be used to pattern the photoresist layer.

(32) To form patterned features **108**, a photoresist layer may be processed in two primary photolithography stages to create a pattern for further processing underlying layers (e.g., intermediate layer **106**): an exposure stage and a development stage. During the exposure stage, the photoresist material reacts to ultraviolet (UV) or other light to form a pattern on the photoresist material. For example, the photoresist layer may be exposed to a pattern of actinic radiation (is irradiated) to form a pattern in the photoresist layer. Actinic radiation may be directed toward semiconductor workpiece **100**, and particularly to a surface of the photoresist layer, possibly through a patterned mask, to cause a target pattern to form in the photoresist layer. The target pattern may include exposed regions and non-exposed regions.

(33) Depending on the type of photoresist material used, portions of the photoresist layer that are exposed to UV light may become more or less soluble in a developer solution, such that those exposed regions may become more difficult or less difficult, respectively, to remove when processed using the developer solution. For example, due to exposure to the UV light, portions of the photoresist that are exposed to the UV light may have different material properties than non-exposed regions of the photoresist. The different material properties may include volatility, reactivity, and/or solubility, for example. During the development stage, the photoresist material is exposed to a developer solution to remove portions of the photoresist layer.

(34) The photoresist material of the photoresist layer may be a positive photoresist or a negative photoresist. For a positive photoresist, areas of the photoresist layer that the semiconductor fabricator intends to remove (and that generally correspond to areas of an underlying layer that will be removed using the structures patterned from the photoresist layer as an etch mask) are exposed to the UV light. The UV light changes the chemical structure of the exposed areas of the photoresist such that the exposed areas become more soluble in a developer solvent that can be used to remove the exposed areas in a development processing stage while the areas of the photoresist that are not exposed remain. For a negative photoresist, portions of the photoresist layer that are exposed to UV polymerize, crosslink, network, or otherwise change chemical composition making the exposed regions less soluble to the developer solution while non-exposed regions can be removed using the developer solution.

(35) In certain embodiments, the photoresist layer may include an agent-generating ingredient (e.g., a photoacid generator (PAG)) that releases a solubility-changing agent (acid, or photoacid) in response to UV light exposure. The generated photoacid may induce further chemical reactions in the photoresist layer, which may improve the tonality in the patterned version of the photoresist layer. For example, in response to exposure to actinic radiation, the agent-generating ingredient (e.g., the PAG) in exposed regions of the photoresist layer may generate a solubility-changing agent (e.g., acid) in exposed regions.

(36) In certain embodiments, semiconductor workpiece **100** is transferred from a photolithography track system to an exposure module (which also may be referred to as a stepper module or scanner module) for exposing the photoresist layer to the pattern of actinic radiation. An example lithography system that includes a projection scanner is described in greater detail below with reference to FIG. 6.

(37) The photoresist layer may be deposited in any suitable manner. For example, the photoresist layer may be deposited by spin-coating, spray-coating, dip-coating, or roll-coating. As a particular example, the photoresist layer may be deposited on semiconductor workpiece **100** using a spin-on deposition technique, which also may be referred to as spin-coating. An example spin-on deposition technique (spin-on deposition technique **114**) is described in greater detail below with reference to FIG. **1B**, and that description is incorporated by reference, with the material of the photoresist layer being substituted as the layer being deposited. It should be understood that this example spin-on deposition technique and associated values are provided as examples only.

(38) In certain embodiments, the photoresist layer is deposited on intermediate layer **106** in a deposition module (e.g., a spin-coating module) of a larger track system for a lithography process. An example lithography system that includes a track system is described in greater detail below with reference to FIG. **6**. It should be understood, however, that the photoresist layer may be deposited using any suitable dry or wet process.

(39) This disclosure contemplates any suitable top coats (e.g., that operate as a diffusion barrier during an immersion lithography technique or serve other suitable purposes) or other layers being deposited on the photoresist layer. As just one example, such a top coat may include a fluorinated polymer.

(40) The photoresist layer may have any suitable thickness, which also may be referred to as height. In certain embodiments, the photoresist layer has a thickness of 5 nm to 5 μ m, for example 20 nm to 1 μ m. Appropriate thickness values may be driven, in part, by the photolithography technology being used to pattern the photoresist layer into patterned features **108**. It should be understood that these thickness values are provided as examples only, and that the photoresist layer may have any suitable thickness. Photoresist structures **109** formed from the photoresist layer might or might not have the same initial height as the photoresist layer, though the height of photoresist structures **109** may change throughout patterning process **102**.

(41) In certain embodiments, a post-exposure bake (PEB) may be performed to modify portions of the photoresist layer to be soluble for development. For example, the PEB may modify portions of the photoresist layer to be soluble in one or more developers for removing the modified portions of the photoresist layer. The portions of the photoresist layer that the PEB solubilizes for development may include the exposed regions of the photoresist layer.

(42) For example, with the previously-executed exposure process, a solubility-changing agent (e.g., acid) has been activated or otherwise generated in the exposed regions of the photoresist layer. The PEB may cause a solubility-changing agent to react with other substances (e.g., a polymer) of the exposed regions to cause the exposed regions to become soluble for development. For example, the PEB may cause a solubility-changing agent to convert one or more of the pendant groups of another substance (e.g., a polymer) of the exposed regions to cause the exposed regions to become soluble for development. This process also may be referred to as a deprotection reaction that causes the exposed regions to become deprotected (e.g., soluble) in a given developer.

(43) In a developing lithography phase, the photoresist layer may be developed using a suitable development process to remove soluble portions of the photoresist layer. During the developing phase, using a positive photolithography process as an example, soluble portions of the photoresist layer may be removed using a suitable dry etch or wet etch process, and thereby forming the photoresist layer into patterned features **108** that can then be used to perform further fabrication process.

(44) For example, development of the photoresist layer (e.g., to remove soluble portions of the photoresist layer **209**) may be performed using an organic solvent. Potential example organic solvents may include propylene glycol methyl ether acetate (PGMEA), 2-Heptanone, isopropyl alcohol (IPA), 2-Pentanone, or another suitable organic solvent. In one example, the solvent dispense volume may be between 5 ml to 500 ml, for example 10 ml to 100 ml. The substrate (e.g., workpiece **100**) may be secured to a rotating chuck that supports the substrate. The rotating speed

during liquid dispense can be between 50 rpm to 3000 rpm, for example 1000 rpm to 2000 rpm. Although organic solvents are primarily described, this disclosure contemplates using any suitable solvent.

(45) As another example, development of the photoresist layer (e.g., to remove soluble portions of the photoresist layer) may be performed in a gas phase with or without plasma. Example gases for such a gas phase may include hydrobromic acid (HBr), boron trichloride (BCL₃), or another suitable gas/gas combination.

(46) The soluble portions of the photoresist layer that are removed during the development phase may include the exposed regions of the photoresist layer. Following removal of the soluble portions of the photoresist layer, unexposed portions of the photoresist layer remain and form photoresist structures **109**. Additionally, removal of soluble portions of the photoresist layer, and particularly the exposed regions, forms recesses **110** in the photoresist layer.

(47) Recesses **110** may be defined by photoresist structures **109**. It should be understood that although two photoresist structures **109** are shown, additional photoresist structures **109** may be formed laterally from the illustrated photoresist structures **109**, partial ones of which are shown at each end of the illustrated semiconductor workpiece **100**. Recesses **110** may have any suitable lateral dimension. Although this disclosure primarily describes “recesses,” other suitable features might be formed in or on a semiconductor substrate, including (whether or not considered “recesses”) lines, holes, trenches, vias, and/or other suitable structures, using embodiments of this disclosure. As a particular example, recesses **110** may be shaped to form slot contacts. Recesses **110** also may be referred to as “spaces.” In the illustrated example, as can be seen in plan view, recesses **110** extend an entire line length of photoresist structures **109**. In other examples, as illustrated in FIG. 2 for example, recesses **110** may extend only a partial length of photoresist structures **109**.

(48) As described above, the lithography technology used to pattern the photoresist layer to form patterned features **108** may have an associated resolution consistent with the wavelength of radiation implemented using that lithography technology. Such photolithography technologies may include dry lithography (e.g., using 193 dry lithography), immersion lithography (e.g., using 193 nanometer immersion lithography), i-line lithography (e.g., using 365 nanometer wavelength UV radiation for exposure), H-line lithography (e.g., using 405 nanometer wavelength UV radiation for exposure), extreme ultraviolet (EUV) lithography, deep ultraviolet (DUV) lithography, or any suitable photolithography. Additionally, the lithography technology may be mask-based (e.g., projection lithography), maskless (e.g., electron beam (e-beam) lithography), or another suitable type of lithography.

(49) As described above, a manufacturer may have a desired width of lines (e.g., photoresist structures **109**) and recesses (e.g., recesses **110**) that is smaller than a width that is directly achievable using a lithography technology that is available to the manufacturer. As a result, an actual width of recesses **110** (W.sub.a) may be larger than a target width of recesses **110** (W.sub.t) by an overage amount (W.sub.a-W.sub.t). Centering the target width (W.sub.t) within a recess **110**, the overage amount is represented as differences D.sub.1 and D.sub.2, with each of D.sub.1 and D.sub.2 representing half the overage amount. Photoresist structures **109** may have any suitable width (R.sub.w1). The widths of lines (e.g., photoresist structures **109**) and spaces (e.g., recesses **110**) also may be referred to as the CD of those features.

(50) To create features having smaller CD than those of photoresist structures **109**, additional processing may be performed. In this particular example, an anti-spacer process may be performed on the semiconductor workpiece **100** of FIG. 1A, with yet further processing performed according to embodiments of this disclosure.

(51) According to the particular example described in connection with FIGS. 1A-1K in which target widths for lines and spaces are 45 nm with a 1:1 line-space ratio, widths (R.sub.w1) of photoresist structures may be 110 nm and actual widths (W.sub.a) of recesses **110** may be 70 nm,

for an initial lithography pitch of 180 nm (110 nm for line width plus 70 nm for recess width), with a target width ($W_{sub.t}$) being 45 nm. Thus, in this example, recesses **110** have widths that are 25 nm larger than the target width, and this difference may be referred to as an overage amount ($D_{sub.1}+D_{sub.2}$). The selection of widths ($R_{sub.w1}$) of photoresist structures **109** to be 110 nm may facilitate forming additional 45 nm features (e.g., for recess **110**) between the region marked for the target width ($W_{sub.t}$) and a 45 nm center portion of photoresist structures **109**. That is, a distance from an edge of a 45 nm center portion of photoresist structures **109** and a nearest edge of the region marked for the target width ($W_{sub.t}$) is 45 nm, 32.5 nm of which is a (to be removed) portion of photoresist structure **109** and 12.5 nm of which is half of an overage amount (e.g., $D_{sub.1}$ or $D_{sub.2}$), and this 45 nm region in this example ultimately will become a recess **110** (e.g., see FIG. 1J).

(52) As shown in FIG. 1B, an overcoat film **112** may be deposited on semiconductor workpiece **100**. Overcoat film **112** may fill recesses **110** and cover photoresist structures **109**. Overcoat film **112** may be a multicomponent material that, as deposited, includes a first component and a second component. The first component could be, for example, a polymer. The second component could be, for example, a solubility-changing agent, such as an acid (e.g., a free acid). The second component could be, as another example, an agent-generating ingredient that, in response to a suitable agent-activation trigger (e.g., heat or radiation), generates a solubility changing agent (e.g., an acid). Example agent-generating ingredients may include a thermal-acid generator (TAG) that is configured to generate acid in response to heat or a PAG that is configured to generate acid in response to actinic radiation. The agent may be a substance that is configured to change the solubility of a material in which the agent is disposed in response to a suitable trigger (e.g., heat), and thus may be referred to as a solubility-changing agent.

(53) Overcoat film **112** may be deposited on semiconductor workpiece **100** in any suitable manner. For example, overcoat film **112** may be deposited by spin-coating, spray-coating, dip-coating, or roll-coating. As a particular example, overcoat film **112** may be deposited on semiconductor workpiece **100** using a spin-on deposition technique **114**, which also may be referred to as spin-coating. Additionally or alternatively, overcoat film **112** may be deposited using a CVD, PECVD, ALD, or other suitable process.

(54) With spin-on deposition, a particular material (e.g., the material of overcoat film **112**) is deposited on a substrate (e.g., semiconductor workpiece **100**). The substrate is then rotated (if not already rotating, possibly at a relatively low velocity) at a relatively high velocity so that centrifugal force causes deposited material to move toward edges of the substrate, thereby coating the substrate. Excess material is typically spun off the substrate. In certain embodiments, spin-on deposition technique **114** includes dispensing liquid chemicals onto semiconductor workpiece **100** (e.g., on a top surface of intermediate layer **106** in recesses **110** and over exposed surfaces of photoresist structures **109**) using a coating module with a liquid delivery system that may dispense one or more types of liquid chemicals. The dispense volume can be between 0.2 ml to 10 ml, for example 0.5 ml to 2 ml. The substrate (e.g., workpiece **100**) may be secured to a rotating chuck that supports the substrate. The rotating speed during liquid dispense can be between 50 rpm to 3000 rpm, for example 1000 rpm to 2000 rpm. The system may also include an anneal module that may bake or apply light radiation to the substrate after the chemicals have been dispensed. It should be understood that this example spin-on deposition technique **114** and associated values are provided as examples only.

(55) In certain embodiments, depending on the configuration and capabilities of the apparatuses involved, and to the extent semiconductor workpiece **100** has not already been transferred back to a track system, deposition of overcoat film **112** may be performed in the exposure system or by another deposition system separate from the exposure system and the track system, or may be performed after transferring semiconductor workpiece **100** from the exposure system back to the track system such that depositing overcoat film **112** (e.g., using spin-on deposition technique **114**)

is performed by a suitable deposition module of the track system. In certain embodiments, overcoat film **112** may be deposited in a deposition module (e.g., a spin-coating module) of a larger track system for a lithography process. An example lithography system that includes a track system is described in greater detail below with reference to FIG. 6.

(56) Overcoat film **112** may have any suitable thickness. In certain embodiments, overcoat film **112** has a thickness of 0.5 nm to 50 nm, for example 5 nm to 100 nm. In certain embodiments, overcoat film **112** is tuned to fill recesses **110** between photoresist structures **109** so that an approximately equal volume of a solubility-changing agent (e.g., solubility-changing agent **117**, described below with reference to FIG. 1C) exists along the sidewalls of photoresist structures **109**. In certain embodiments, a thickness of overcoat film **112** depends at least in part on a thickness of photoresist structures **109**, as overcoat film **112** may be sufficiently thick to fill recesses **110** and cover photoresist structures **109**. It should be understood that these thickness values are provided as examples only, and that overcoat film **112** may have any suitable thickness.

(57) As shown in FIG. 1C, a bake **116** of semiconductor workpiece **100** may be performed. Baking semiconductor workpiece **100** may cause a solubility-changing agent **117** (e.g., acid) of overcoat film **112** to diffuse into a portion of photoresist structures **109** and to cause those portions of photoresist structures **109** to become soluble in a developer, thereby forming soluble portions **118** of photoresist structures **109**. Portions of photoresist structures **109** that remain insoluble in the developer (e.g., portions into which solubility-changing agent **117** did not diffuse) may be referred to as insoluble portions **119**.

(58) For example, in the case of overcoat film **112** including a free acid, solubility-changing agent **117** may be the free acid and baking semiconductor workpiece **100** may cause solubility-changing agent **117** to diffuse into a portion of photoresist structures **109** and to cause those portions of photoresist structures **109** to become soluble in a developer.

(59) As another example, in the case of overcoat film **112** including a TAG as an agent-generating ingredient, baking semiconductor workpiece **100** may cause the TAG to generate solubility-changing agent **117** (which may be referred to as activating the acid), cause the generated solubility-changing agent **117** to diffuse into a portion of photoresist structures **109**, and cause those portions of photoresist structures **109** to become soluble in a developer. For example, the TAG may generate solubility-changing agent **117** within overcoat film **112** in response to heat. Thus, in certain embodiments, the heat associated with bake **116** both causes the agent-generating ingredient (e.g., a TAG) in overcoat film **112** to generate solubility-changing agent **117** within overcoat film **112** and causes the generated solubility-changing agent **117** to diffuse into and change the solubility of suitable portions of photoresist structures **109**.

(60) As another example, in the case of overcoat film **112** including a PAG as an agent-generating ingredient, an exposure step that includes exposing overcoat film **112** to radiation may be performed prior to baking semiconductor workpiece **100** (e.g., prior to executing bake **116**). The PAG may generate solubility-changing agent **117** in response to the exposure to radiation (which may be referred to as activating the acid). Bake **116** may cause the generated solubility-changing agent **117** to diffuse into a portion of photoresist structures **109**, and cause those portions of photoresist structures **109** to become soluble in a developer.

(61) The exposure suitable for causing the PAG to generate solubility-changing agent may be a flood exposure or may be more similar to the exposure used to form photoresist structures **109** in FIG. 1A. In the case of a flood exposure, it may be possible to perform the exposure in an on-track module of a track-based lithography system without moving semiconductor workpiece **100** to a stepper for more complex exposure. In the case of a more complex exposure, semiconductor workpiece **100** may be moved to a stepper for exposure and then returned to the track. This disclosure contemplates performing the exposure step in any suitable manner.

(62) Of course, this disclosure contemplates including other suitable types of agent-generating ingredients that generate solubility-changing agent **117** in response to a suitable activation trigger

(e.g., heat, radiation, or another suitable trigger), if appropriate.

(63) Baking semiconductor structures **100** generally causes solubility-changing agent **117** to diffuse into perimeter portions of photoresist structures **109** to a target depth, and to modify those perimeter portions to be soluble in a developer, forming soluble portions **118**. Bake **116** may be executed to achieve the target depth of diffusion of solubility-changing agent **117** (e.g., acid) into perimeter portions of photoresist structures **109** to cause those portions of photoresist structures **109** to become soluble for subsequent development, as described in greater detail with reference to FIG. **1F**. The target depth of diffusion could be, for example, a target depth of diffusion into perimeter portions of photoresist structures **109** (forming soluble portions **118**) to ultimately cause a thinning, or reduction in width (and possibly height), of photoresist structures **109** by the amount of the target depth.

(64) For example, the modified perimeter portions (soluble portions **118**) may form a deprotected/soluble shell-like structure around insoluble portions **119** of photoresist structures **109**, consuming a portion of an outer perimeter of photoresist structures **109** and thereby, when removed via a development process, reducing both a vertical and lateral dimension of photoresist structures **109**. Among other factors, baking time and/or temperature may be optimized to control a depth of diffusion of solubility-changing agent **117** to achieve the target depth. The depth of diffusion of solubility-changing agent **117** into photoresist structures **109** may be the same or different in the vertical and lateral dimensions.

(65) Insoluble portions **119** of photoresist structures **109** remain insoluble in the developer. Insoluble portions **119** of photoresist structures **109** also may be referred to as remaining portions of photoresist structures **109** (e.g., remaining, following development at a subsequent stage). Insoluble portions **119** may have a reduced width (and possibly height/thickness) relative to a width of photoresist structures **109**.

(66) The depth of diffusion of solubility-changing agent **117** into photoresist structures **109** may be deliberately designed and controlled to achieve a desired width reduction of photoresist structures **109** when developed. In the illustrated example, a lateral depth of diffusion (e.g., on sidewall surfaces of photoresist structures **109**) of solubility-changing agent **117** into photoresist structures **109** is shown as $D_{sub.d1}$ and $D_{sub.d2}$ such that, after development in a subsequent step, widths ($R_{sub.w1}$) of photoresist structures **109** are reduced by $D_{sub.d1} + D_{sub.d2}$ and insoluble portions **119** of photoresist structures **109** have a width $R_{sub.w2}$. For example, insoluble portions **119** of photoresist structures **109** have a reduced width, shown as $R_{sub.w2}$, relative to the width $R_{sub.w1}$ of photoresist structures **109** in FIG. **1A**, and a difference between $R_{sub.w1}$ and $R_{sub.w2}$ represents a depth of diffusion ($D_{sub.d1} + D_{sub.d2}$) of solubility-changing agent **117**, at least in a lateral dimension. In certain embodiments, the depth of diffusion, and resulting change in solubility of portions of photoresist structures **109**, is approximately equal on all sides of photoresist structures **109**. The lateral depth of diffusion of solubility-changing agent **117** into portions of photoresist structures **109** ($D_{sub.d1}$ and $D_{sub.d2}$) could also be referred to as a lateral thickness of soluble portions **118**.

(67) Soluble portions **118** also include a vertical component, which may be any suitable amount according to particular implementations. In other words, solubility-changing agent **117** may diffuse by a vertical depth of diffusion into photoresist structures **109** (e.g., on top surfaces of photoresist structures **109**) such that following development heights of patterned features **108** are reduced to heights of insoluble portions **119**.

(68) A target lateral depth of diffusion of solubility-changing agent **117** into photoresist structures **109** (e.g., target values for $D_{sub.d1}$ and $D_{sub.d2}$) may depend on a variety of factors. Due to the potential dependence on other steps of patterning process **102**, a depth of diffusion of solubility-changing agent **117** into photoresist structures **109** is described in greater detail following the description of FIG. **1J**. In short, however, a lateral depth of diffusion of solubility-changing agent **117** into photoresist structures **109** may depend on whether subsequent steps of patterning process

102 are expected to further reduce a lateral dimension (width) of photoresist structures **109**.

(69) To the extent subsequent steps of patterning process **102** are not expected to further reduce a lateral dimension (width) of photoresist structures **109**, then a lateral depth of diffusion of solubility-changing agent **117** into photoresist structures **109** (D.sub.d1+D.sub.d2) may be sufficient such that widths of insoluble portions **119** (R.sub.w2) are a target width for a CD of photoresist structures **109**. For the particular example described in connection with FIGS. **1A-1J**, in a scenario in which subsequent steps of patterning process **102** are not expected to further reduce a lateral dimension (width) of photoresist structures **109**, depths of diffusion of solubility-changing agent **117** into photoresist structures **109** may be 32.5 nm (45 nm minus $\frac{1}{2}$ the overage amount (one-half being D.sub.d1 or D.sub.d2), or 12.5 in this example) laterally on each side of photoresist structures **109**, which, following subsequent development, will bring the width R.sub.w2 of the photoresist structures **109** to the target width of 45 nm (110 nm minus 32.5 nm (on a first side of photoresist structure **109**) minus 32.5 nm (on a second side of photoresist structure **109**)).

(70) To the extent subsequent steps of patterning process **102** are expected to further reduce a lateral dimension (width) of photoresist structures **109**, then a lateral depth of diffusion of solubility-changing agent **117** into photoresist structures **109** (D.sub.d1+D.sub.d2) may be biased to account of this expected future reduction such that the lateral depth of diffusion at FIG. **1C** is less than a full amount of diffusion that would result in widths of insoluble portions **119** (R.sub.w2) being a target width for CDs of photoresist structures **109**. For the particular example described in connection with FIGS. **1A-1J**, in a scenario in which subsequent steps of patterning process **102** are expected to further reduce a lateral dimension (width) of photoresist structures **109** (e.g., in FIGS. **1I-1J**), depths of diffusion of solubility-changing agent **117** into photoresist structures **109** may be less than 32.5 nm (45 nm minus $\frac{1}{2}$ the overage amount (one-half being D.sub.d1 or D.sub.d2), or 12.5 in this example) laterally on each side of photoresist structures **109** by an amount equal to one-half the expected amount of future reduction in width of photoresist structures **109** (specifically, future reduction in width of photoresist structures **109'** in FIGS. **1I-1J**).

(71) In other words, as a result of forming soluble portions **118** and insoluble portions **119** at the stage illustrated in FIG. **1C**, widths of insoluble portions **119** (R.sub.w2) might be a final target width (CD) (45 nm in one example) for photoresist structures **109** or might be greater than target widths (CD) for photoresist structures **109**.

(72) Concentration of solubility-changing agent **117** (e.g., acid), diffusivity of solubility-changing agent **117**, and process parameters of bake **116** may influence one another and be tuned for a particular process. A general concentration range for the solubility changing agent may be 2-10% of the total film solids. Molecular weight and sterics based on the structure of solubility-changing agent **117** (e.g., compact organic groups vs. nodular such as spokes on a wheel) may be primary influencers of diffusivity of solubility-changing agent **117**. An example diffuse super acid used in photoresist technology may include trifluoromethane sulfonic acid. An example mid-range diffusive acid may be perfluorobutane sulfonic acid. Examples of a low diffusivity acid may include perfluorooctane sulfonic acid and p-trifluoromethane benzene sulfonic acid.

(73) In certain embodiments, bake **116** may be performed by heating semiconductor workpiece **100** in a process chamber at a temperature between 50° C. to 250° C., for example between 60° C. to 120° C. in certain embodiments, in vacuum or under a gas flow. In a particular example, semiconductor workpiece **100** is baked for 1 to 3 minutes. The bake conditions of bake **116** may be selected to promote the diffusion of solubility-changing agent **117** (and possibly generation of the solubility-changing agent **117** from an agent-generating ingredient of overcoat film **112**, if applicable) and associated change in solubility of a perimeter of photoresist structures **109** to the target depth. This disclosure contemplates executing bake **116** in any suitable manner.

(74) As illustrated in FIG. **1D**, overcoat film **112** may be removed selectively from semiconductor workpiece **100**, with minimal to no removal of photoresist structures **109**, including little to no removal of soluble portions **118** and insoluble portions **119** of photoresist structures **109**. This

disclosure contemplates selectively removing overcoat film **112** in any suitable manner. In certain embodiments, overcoat film **112** may be removed selectively from semiconductor workpiece **100** using a suitable solvent wash **121** or other developer, with the solvent being selective to removing overcoat film **112**.

(75) In certain embodiments, solvent wash **121** may be performed using a solvent of 4-methyl-2-pentanol or diisoamyl ether to selectively remove overcoat film **112**. Although this disclosure describes particular solvents for solvent wash **121**, this disclosure contemplates using any suitable solvent for solvent wash **121**.

(76) In certain embodiments, with the selective removal of overcoat film **112**, at this state of patterning process **102**, recesses **110** have been re-revealed and continue to have an actual width (W.sub.a) that exceeds a target width (W.sub.t). For the particular example described in connection with FIGS. **1A-1J**, at the state illustrated in FIG. **1D**, recesses **110** have an actual width (W.sub.a) of 70 nm that exceeds target width (W.sub.t) of 45 nm.

(77) As illustrated in FIG. **1E**, an overcoat film **120** may be deposited on semiconductor workpiece **100**. Overcoat film **120** may fill recesses **110** and cover photoresist structures **109**, including over soluble portions **118** of photoresist structures **109**.

(78) Overcoat film **120** may be deposited on semiconductor workpiece **100** in any suitable manner. For example, overcoat film **120** may be deposited by spin-coating, spray-coating, dip-coating, or roll-coating. As a particular example, overcoat film **120** may be deposited on semiconductor workpiece **100** using a spin-on deposition technique **114**, in a similar manner to that described above with reference to overcoat film **112** in FIG. **1B**. The description of spin-on deposition technique **114** from FIG. **1B** is incorporated by reference, with the material of overcoat film **120** replacing the material of overcoat film **112**. Additionally or alternatively, overcoat film **120** may be deposited using a CVD, PECVD, ALD, or other suitable process.

(79) In certain embodiments, overcoat film **120** may be deposited in a deposition module (e.g., a spin-coating module) of a larger track system for a lithography process. An example lithography system that includes a track system is described in greater detail below with reference to FIG. **6**.

(80) In certain embodiments, overcoat film **120** may include a polymer material and a crosslinking agent. As particular examples, overcoat film **120** may include mixtures distributed under the classification of developable bottom anti-reflective coating (DBARC) materials. In response to a suitable trigger (e.g., a suitable amount of heat), the crosslinking agent may react with the polymer material to cause the material of overcoat film **120** to harden. As an example, the crosslinking agent may include a vinyloxy group and/or an N-methoxymethylamide group as a reactive group. For example, the vinyloxy group may promote crosslinking (e.g., at least in part via formation of an acetal bond) with carboxyl groups and/or phenolic hydroxyl groups in the polymer material of overcoat film **120**. Example crosslinking is described below with reference to FIG. **1G**.

(81) Overcoat film **120** may have any suitable thickness. In certain embodiments, overcoat film **120** has a thickness of 0.5 nm to 5 μ m, for example 20 nm to 1 μ m. In certain embodiments, overcoat film **120** is tuned to fill recesses **110** between photoresist structures **109**. In certain embodiments, a thickness of overcoat film **120** depends at least in part on a thickness of photoresist structures **109**, as overcoat film **120** may be sufficiently thick to fill recesses **110** and cover photoresist structures **109**. It should be understood that these thickness values are provided as examples only, and that overcoat film **120** may have any suitable thickness.

(82) As illustrated in FIG. **1F**, soluble portions **118** of photoresist structures **109** and portions of overcoat film **120** may be removed selectively to reveal patterned features **123**. Patterned features **123** may include insoluble portions **119** of photoresist structures **109**, overcoat structures **122** remaining from overcoat film **120**, and recesses **124**. This disclosure contemplates removing soluble portions **118** of photoresist structures **109** and the portions of overcoat film **120** in any suitable manner.

(83) In certain embodiments, the portions of overcoat film **120** and soluble portions **118** of

photoresist structures **109** are removed selectively using a developer. For example, the developer may remove sufficient portions of overcoat film **120** to reveal soluble portions **118** of photoresist structures **109**, and then remove those soluble portions **118** of photoresist structures **109** at a more rapid removal rate (e.g., dissolution rate). As a particular example, the developer may remove at a first removal rate sufficient portions of overcoat film **120** to reveal soluble portions **118** of photoresist structures **109**, and then remove those soluble portions **118** of photoresist structures **109** at a greater second removal rate. In certain embodiments, the second removal rate is significantly larger than the first removal rate (**1000:1**, as a non-limiting example) such that once soluble portions **118** of photoresist structures **109** are revealed, those soluble portions **118** of photoresist structures **109** are removed much more rapidly than additional removal of portions of overcoat film **120**.

(84) In certain embodiments, the portions of overcoat film **120** and soluble portions **118** of photoresist structures **109** are removed selectively in a wet process by treating semiconductor workpiece **100** with a developer solution to dissolve the portions of overcoat film **120** and soluble portions **118** of photoresist structures **109**. The appropriate developer solution may depend in part on the material of overcoat film **120** and soluble portions **118** of photoresist structures **109**. In certain embodiments, the developer solution may include an aqueous alkaline solution that includes a water-soluble organic base. As particular examples, the developer solution may include tetramethylammonium hydroxide (TMAH).

(85) Alternatively, a dry process may be used in other embodiments. The dry process may include, for example, a selective plasma etch process or a thermal process, which may eliminate the use of a developing solution. In certain embodiments, the dry process may be performed using reactive ion etching (RIE) process or atomic layer etching (ALE).

(86) Removal of soluble portions **118** of photoresist structures **109** forms photoresist structures **109'** formed from insoluble portions **119** of photoresist structures **109**. Additionally, removal of the portions of overcoat film **120** and soluble portions **118** of photoresist structures **109** forms overcoat structures **122** from overcoat film **120** (e.g., remaining portions of overcoat film **120**). Removing soluble portions **118** of photoresist structures **109** reveals recesses **124** defined by overcoat structures **122** and photoresist structures **109'**. In this example, at the state illustrated in FIG. 1F, overcoat structures **122** occupy the space of previous recesses **110**, and recesses **124** occupy the space of soluble portions **118** of photoresist structures **109**. At the state illustrated in FIG. 1F, photoresist structures **109'** have a width $R_{sub.w2}$, overcoat structures **122** have a width $W_{sub.a}$, and recesses **124** have a width $D_{sub.d1}$ or $D_{sub.d2}$ (e.g., $D_{sub.d1}$ and $D_{sub.d2}$ may be equal). Furthermore, at the state illustrated in FIG. 1F, while photoresist structures **109'** potentially have a target width (e.g., a target CD of patterning process **102**), depending on a depth of diffusion of solubility-changing agent **117** at the state illustrated in FIG. 1C and subsequent removal of soluble portions **118** at the state illustrated in FIG. F, recesses **124** are narrower than a target width and overcoat structures **122** are wider than a target width (e.g., $W_{sub.t}$).

(87) For the particular example described in connection with FIGS. 1A-1J, at the state illustrated in FIG. 1F, a width of photoresist structures **109'** may be 45 nm (the target CD in this example), a width of overcoat structures **122** may be 70 nanometers (the actual width $W_{sub.a}$ of recesses **110** that where overcoat structures **122** now are formed), and a width of recesses **124** may be 32.5 nm. Thus, in this example, photoresist structures **109'** have the target width, overcoat structures **122** are wider than the target width, and recesses **124** are narrower than the target width.

(88) As illustrated in FIG. 1G, a bake **125** of semiconductor workpiece **100** may be performed. Baking semiconductor workpiece **100** may cause a solubility-changing reaction to occur in overcoat structures **122** (formed from overcoat film **120**). Thus, in certain embodiments, the solubility-changing reaction is a thermally-induced solubility-changing reaction.

(89) This solubility-changing reaction may have one or more effects. For example, the solubility-changing reaction may cause overcoat structures **122** to become insoluble in a casting solvent that

is used in a subsequent step of patterning process **102** in which an additional overcoat film is deposited (e.g., as illustrated in and described below with reference to FIG. **1H**). As another example, the solubility-changing reaction may cause overcoat structures **122** to become insoluble in a developer used in a subsequent step to remove that additional overcoat film and to-be-modified portions of overcoat structures **122** (e.g., as illustrated in and described below with reference to FIG. **1J**).

(90) In an example in which overcoat film **120**, and particularly overcoat structures **122** that remain from overcoat film **120**, includes a polymer, the solubility-changing reaction caused by bake **125** may include polymer crosslinking in overcoat structures **122**, the polymer crosslinking rendering overcoat structures **122** insoluble in a casting solvent used in a subsequent step of patterning process **102** and/or in a developer used in a subsequent step, as described above. For example, polymer chains of overcoat structures **122** may be crosslinked via bond formation induced by heat. In certain embodiments, the crosslinking may include C—C bond formation or S—S bond formation among others. As just one particular example, overcoat film **120** may include hydroxystyrene that may undergo crosslinking in response to adequate heat.

(91) In addition to or in place of bake **125**, in certain embodiments, the solubility-changing reaction of FIG. **1G** may be a photoinduced solubility-changing reaction. For example, irradiating semiconductor workpiece **100** (e.g., exposing overcoat film **120**, and particularly overcoat structures **122**, to actinic radiation) may cause a solubility-changing reaction to occur in overcoat structures **122**. If appropriate, the irradiation may be accompanied by executing bake **125**. In an example in which overcoat film **120**, and particularly overcoat structures **122** that remain from overcoat film **120**, includes a polymer, the solubility-changing reaction caused by exposure (possibly with an accompanying bake **125**) may include polymer crosslinking in overcoat structures **122**, the polymer crosslinking rendering overcoat structures **122** insoluble in a casting solvent used in a subsequent step of patterning process **102** and/or in a developer used in a subsequent step, as described above. For example, polymer chains of overcoat structures **122** may be crosslinked via bond formation induced by actinic radiation exposure. In certain embodiments, the crosslinking may include C—C bond formation or S—S bond formation among others. Such bond formations may be catalyzed by a photoacid generated by the actinic radiation exposure. As just one particular example, overcoat film **120** may include hydroxystyrene that may undergo crosslinking in response to actinic radiation exposure.

(92) The exposure suitable for causing the solubility-changing reaction to occur in overcoat structures **122** may be a flood exposure or may be more similar to the exposure used to form photoresist structures **109** in FIG. **1A**. In the case of a flood exposure, it may be possible to perform the exposure in an on-track module of a track-based lithography system without moving semiconductor workpiece **100** to a stepper for more complex exposure. In the case of a more complex exposure, semiconductor workpiece **100** may be moved to a stepper for exposure and then returned to the track. Of course, this disclosure contemplates performing the exposure step in any suitable manner.

(93) To the extent bake **125** is performed, in certain embodiments, bake **125** may be performed by heating semiconductor workpiece **100** in a process chamber at a temperature between 50° C. to 250° C., for example between 80° C. to 140° C. in certain embodiments, in vacuum or under a gas flow. In certain embodiments, bake **125** is performed at a higher temperature than bake **116**, such as at an approximately 20° C. higher temperature. In a particular example, semiconductor workpiece **100** is baked for 1 to 3 minutes. The bake conditions of bake **125** may be selected to promote the solubility-changing reaction (e.g., crosslinking of the polymer of overcoat structures **122**). This disclosure contemplates executing bake **125** in any suitable manner.

(94) As illustrated in FIG. **1H**, an overcoat film **126** may be deposited on semiconductor workpiece **100**. Overcoat film **126** may fill recesses **124** and cover photoresist structures **109'** and overcoat structures **122**. In certain embodiments, overcoat film **126** is a similar material to overcoat film

112. Overcoat film **126** may be a multicomponent material that, as deposited, includes a first component and a second component. The first component could be, for example, a polymer. The second component could be, for example, a solubility-changing agent, such as an acid (e.g., a free acid). The second component could be, as another example, an agent-generating ingredient that, in response to a suitable agent-activation trigger (e.g., heat or radiation), generates a solubility changing agent (e.g., an acid). Example agent-generating ingredients may include a TAG that is configured to generate acid in response to heat or a PAG that is configured to generate acid in response to actinic radiation. The agent may be a substance that is configured to change the solubility of a material in which the agent is disposed in response to a suitable trigger (e.g., heat), and thus may be referred to as a solubility-changing agent.

(95) Overcoat film **126** may be deposited on semiconductor workpiece **100** in any suitable manner. For example, overcoat film **126** may be deposited by spin-coating, spray-coating, dip-coating, or roll-coating. As a particular example, overcoat film **126** may be deposited on semiconductor workpiece **100** using a spin-on deposition technique **114**, in a similar manner to that described above with reference to overcoat film **112** in FIG. **1B**. The description of spin-on deposition technique **114** from FIG. **1B** is incorporated by reference, with the material of overcoat film **126** replacing the material of overcoat film **112**. Additionally or alternatively, overcoat film **126** may be deposited using a CVD, PECVD, ALD, or other suitable process.

(96) In certain embodiments, overcoat film **126** may be deposited in a deposition module (e.g., a spin-coating module) of a larger track system for a lithography process. An example lithography system that includes a track system is described in greater detail below with reference to FIG. **6**.

(97) Overcoat film **126** may have any suitable thickness. In certain embodiments, overcoat film **126** has a thickness of 0.5 nm to 5 μm , for example 20 nm to 1 μm . In certain embodiments, overcoat film **126** is tuned to fill recesses **124** between photoresist structures **109'** and overcoat structures **122** so that an approximately equal volume of a solubility-changing agent (e.g., solubility-changing agent **128**, described below with reference to FIG. **1I**) exists along the sidewalls of photoresist structures **109'** and overcoat structures **122**. In certain embodiments, a thickness of overcoat film **126** depends at least in part on a thickness of photoresist structures **109'** and overcoat structures **122**, as overcoat film **126** may be sufficiently thick to fill recesses **124** and cover photoresist structures **109'** and overcoat structures **122**. It should be understood that these thickness values are provided as examples only, and that overcoat film **126** may have any suitable thickness.

(98) As shown in FIG. **1I**, a bake **127** of semiconductor workpiece **100** may be performed. Baking semiconductor workpiece **100** may cause a solubility-changing agent **128** (e.g., acid) to diffuse into portions of overcoat structures **122** and to cause those portions of overcoat structures **122** to become soluble in a developer.

(99) For example, if overcoat film **126** includes a free acid, solubility-changing agent **128** may be the free acid and baking semiconductor workpiece **100** may cause solubility-changing agent **128** (e.g., acid) to diffuse into portions of overcoat structures **122** and to cause those portions of overcoat structures **122** to become soluble in a developer.

(100) As another example, if overcoat film **126** includes a TAG as an agent-generating ingredient, baking semiconductor workpiece **100** may cause the TAG to generate solubility-changing agent **128** (e.g., acid), which may be referred to as activating the acid, cause the generated solubility-changing agent **128** (e.g., acid) to diffuse into portions of overcoat structures **122**, and cause those portions of overcoat structures **122** to become soluble in a developer.

(101) As another example, if overcoat film **126** includes a PAG as an agent-generating ingredient, overcoat film **126** may be exposed to radiation prior to baking semiconductor workpiece **100** (e.g., prior to executing bake **127**). This exposure step may cause the PAG to generate solubility-changing agent **128** (e.g., acid), which may be referred to as activating the acid. Baking semiconductor workpiece **100** using bake **127** may cause the generated solubility-changing agent **128** (e.g., acid) to diffuse into portions of overcoat structures **122**, and cause those portions of

overcoat structures **122** to become soluble in a developer.

(102) The exposure suitable for causing the PAG to generate solubility-changing agent **128** may be a flood exposure or may be more similar to the exposure used to form photoresist structures **109** in FIG. **1A**. In the case of a flood exposure, it may be possible to perform the exposure in an on-track module of a track-based lithography system without moving semiconductor workpiece **100** to a stepper for more complex exposure. In the case of a more complex exposure, semiconductor workpiece **100** may be moved to a stepper for exposure and then returned to the track. The exposure step may be performed in any suitable manner.

(103) Of course, this disclosure contemplates including other suitable types of agent-generating ingredients that generate solubility-changing agent **128** in response to a suitable activation trigger (e.g., heat, radiation, or another suitable trigger), if appropriate.

(104) Baking semiconductor structures **100** generally causes solubility-changing agent **128** to diffuse into perimeter regions of overcoat structures **122** to a target depth, and to modify that perimeter region to be soluble in a developer, forming soluble portions **130** of overcoat structures **122**. For example, the modified perimeter regions (soluble portions **130**) may form a deprotected/soluble shell-like structure around overcoat structures **122**, consuming a portion of an outer perimeter of overcoat structures **122** and thereby reducing both a vertical and lateral dimension of overcoat structures **122**. Among other factors, baking time and/or temperature may be optimized to control a depth of diffusion of solubility-changing agent **128** to achieve the target depth. The depth of diffusion of solubility-changing agent **128** into overcoat structures **122** may be the same or different in the vertical and lateral dimensions. Insoluble portions **132** of overcoat structures **122** remain insoluble in the developer.

(105) In the illustrated example, a lateral depth of diffusion (e.g., on sidewall surfaces of overcoat structures **122**) of solubility-changing agent **128** into overcoat structures **122** is shown as D.sub.1 and D.sub.2 (the overage amount of recesses **110** in FIG. **1A**, or half the overage amount of recesses **110** on each side of overcoat structures **122**) such that a widths (W.sub.t) of overcoat structures **122** are reduced by D.sub.1+D.sub.2 and insoluble portions **132** of overcoat structures **122** have widths W.sub.t (e.g., the original target width of recesses **110**). For example, insoluble portions **132** have a reduced width, shown as W_e, relative to the width W_a of overcoat structures **122**, and a difference between W_a and W.sub.t represents a depth of diffusion (D.sub.1+D.sub.2) of solubility-changing agent **128** and soluble portions **130**, at least in a lateral dimension. In certain embodiments, the depth of diffusion, and resulting change in solubility of soluble portion **130**, is approximately equal on all sides of overcoat structures **122**. The lateral depth of diffusion of solubility-changing agent **128** into overcoat structures **122** (D.sub.1 and D.sub.2) could also be referred to as a lateral thickness of soluble portions **130**. Soluble portions **130** also include a vertical component, which may be any suitable amount according to particular implementations. In other words, solubility-changing agent **128** may diffuse by a vertical depth of diffusion into overcoat structures **122** (e.g., on top surfaces of overcoat structures **122**) such that heights of overcoat structures **122** are reduced to a height of insoluble portions **132**.

(106) As described above, in certain embodiments, solubility-changing agent **128** also may diffuse into portions of photoresist structures **109'** to further reduce a later dimension (and/or potentially a vertical dimension) of photoresist structures **109'**, modifying the portions of photoresist structures **109'** into which solubility-changing agent **128** diffuses soluble for development. To the extent patterning process **102** is designed for solubility-changing agent **128** to diffuse into portions of photoresist structures **109'**, an adjustment may be made to the target diffusion amount of solubility-changing agent **117** into photoresist structures **109** (as illustrated in FIG. **1C**) to account for this additional diffusion so that a final width of photoresist structures **109'** and recesses **124** equal a target amount.

(107) For the particular example described in connection with FIGS. **1A-1J**, at the state illustrated in FIG. **1I**, a depth of diffusion of solubility-changing agent **128** into overcoat structures **122** (e.g.,

a width of soluble portions **130**) may be 12.5 nm on each side of overcoat structures **122** to thereby reduce a width of overcoat structures **122** by the overage amount ($D_{sub.1} + D_{sub.2}$) of 25 nm.

(108) In certain embodiments, bake **127** may be performed by heating semiconductor workpiece **100** in a process chamber at a temperature between 50° C. to 250° C., for example between 60° C. to 120° C. in certain embodiments, in vacuum or under a gas flow. In a particular example, semiconductor workpiece **100** is baked for 1 to 3 minutes. The bake conditions of bake **127** may be selected to promote the diffusion of solubility-changing agent **128** (and possibly generation of the solubility-changing agent **128** from an agent-generating ingredient of overcoat film **126**, if applicable) and associated change in solubility of a perimeter of overcoat structures **122** to the target depth. This disclosure contemplates executing bake **127** in any suitable manner.

(109) As illustrated in FIG. 1J, overcoat film **126** and soluble portions **130** of overcoat structures **122** may be removed selectively to reveal patterned features **134**. Patterned features **134** may include photoresist structures **109''**, overcoat structures **122'** (insoluble portions **132** of overcoat structures **122**), and recesses **124'**. To the extent portions of photoresist structures **109'** were modified via diffusion of solubility-changing agent **128** in FIG. 1I, those modified portions of photoresist structures **109'** also may be removed selectively to reveal photoresist structures **109''**. This disclosure contemplates removing overcoat film **126** and soluble portions **130** of overcoat structures **122** (and, to the extent applicable, modified portions of photoresist structures **109'**) in any suitable manner. For the remainder of the description of FIG. 1J, this disclosure assumes that no portions of photoresist structures **109'** were designed to be modified by solubility-changing agent **128** in FIG. 1I. In certain embodiments, overcoat film **126** and soluble portions **130** of overcoat structures **122** are removed selectively using a developer.

(110) In certain embodiments, overcoat film **126** and soluble portions **130** of overcoat structures **122** are removed selectively in a wet process by treating semiconductor workpiece **100** with a developer solution to dissolve selectively overcoat film **126** and soluble portions **130** of overcoat structures **122**. The appropriate developer solution for selectively removing overcoat film **126** and soluble portions **130** of overcoat structures **122** depends in part on the material of overcoat film **126** and soluble portions **130** of overcoat structures **122**. In certain embodiments, the developer solution may include an aqueous alkaline solution that includes a water-soluble organic base. As particular examples, the developer solution may include TMAH.

(111) Alternatively, a dry process may be used in other embodiments. The dry process may include, for example, a selective plasma etch process or a thermal process, which may eliminate the use of a developing solution. In certain embodiments, the dry process may be performed using an RIE process or an ALE process.

(112) Removing overcoat film **126** and soluble portions **130** of overcoat structures **122** forms patterned structures **122'** from insoluble portions **132** of overcoat structures **122** (remaining portions of overcoat structures **122**) and re-reveals photoresist structures **109'** (labeled as photoresist structures **109''** to the extent portions of photoresist structures **109'** also may be solubilized and removed at FIGS. 1I and 1J). Removing soluble portions **130** of overcoat structures **122** to form overcoat structures **122'** reduces a width of overcoat structures **122** from $W_{sub.a}$ (of overcoat structures **122**) to target width $W_{sub.t}$ (of overcoat structures **122'**).

(113) Removing soluble portions **130** of overcoat structures **122** reveals recesses **124'** defined by overcoat structures **122'** and photoresist structures **109''**. Recesses **124'** have a width $D_{sub.2} + D_{sub.d1}$ (or $D_{sub.1} + D_{sub.d2}$), shown as width $S_{sub.w}$. For example, removing soluble portions **130** of overcoat structures **122** expands a width of recesses **124** from a width $D_{sub.d1}$ (or $D_{sub.d2}$) (of recesses **124**) to a width $D_{sub.2} + D_{sub.d1}$ (or $D_{sub.1} + D_{sub.d2}$) (of recesses **124'**), which may be the target width for recesses **124'**.

(114) Thus, at the state illustrated in FIG. 1J, patterned features **134**, including photoresist structures **109''**, overcoat structures **122'**, and recesses **124'** have reached respective target widths. Those respective target widths are sub-resolution widths relative to feature widths that may be

directly achieved with the lithography technology used to form patterned features **108** in FIG. **1A**. Additionally, in this example, a feature pitch that might be accomplished using a standard anti-spacer patterning process has been reduced, thereby increasing a feature density of semiconductor workpiece **100**. In the illustrated example, a feature pitch for a line-space-line-space pattern is 1:1:1:1; however, this disclosure contemplates other feature pitches.

(115) For the particular example described in connection with FIGS. **1A-1J**, at the state illustrated in FIG. **1J**, widths of photoresist structures **109''**, widths of overcoat structures **122'**, and widths of recesses **124'** are 45 nm, and a feature pitch for a line(photoresist structure **109''**)-space(recess **124'**)-line(overcoat structure **122'**)-space (recess **124'**) pattern is 1:1:1:1.

(116) Having described the partial development of overcoat film **120** in FIG. **1F** (to form overcoat structures **122**), the conversion of overcoat structures **122** to be insoluble in a developer in FIG. **1G**, the conversion of portions of overcoat structures **122** to be soluble for development in FIG. **1I**, and the development of those soluble portions of overcoat structures **122** in FIG. **1J**, one can understand that, in certain embodiments, overcoat film **120** has a switchable solubility for a developer solution that may be activated by a diffusible solubility-changing agent. For example, overcoat film **120** may include polymer resin to facilitate this switchable solubility.

(117) In certain embodiments, the polymer resin may be designed with the following characteristics: 1) a low minimum development rate ($R_{sub.min}$) in the developer to reveal recesses **124** in FIG. **1F** (e.g., the anti-spacer trenches) and thereby allow for a controlled recess of overcoat film **120**; 2) the polymer resin is functionalized such that a thermally-activated or photo-activated reaction prevents or otherwise inhibits dissolution of overcoat film **120** in a casting solvent for depositing overcoat film **126** (FIG. **1H**) or dissolution in a developer for forming patterned features **134** (FIG. **1J**); and 3) diffusion of a reactive species (solubility-changing agent **128**, such as acid) into the polymer resin causes a solubility shift resulting in the reacted resin having a high $R_{sub.min}$ in the developer solvent. As described above, in certain embodiments, the crosslinking of overcoat film **120** (e.g., overcoat structures **122**) may be thermally initiated for the sake of throughput/cost (e.g., FIG. **1G**), and the decrosslinking (solubilization) mechanism may occur through reaction with a strong acid (e.g., FIG. **1I**), such as a free acid, an acid generated from a TAG, or an acid generated from a PAG.

(118) Additionally, returning to the diffusion of solubility-changing agent **117** into photoresist structures **109** (FIG. **1C**), a target amount of lateral diffusion for a given implementation may depend on whether a solubility-changing agent **128** (with associated process conditions) is designed to diffuse into photoresist structures **109'** (FIG. **1I**) such that widths of photoresist structures **109'** will undergo a further width adjustment at the stages illustrated in FIGS. **1I-1J**, or if instead solubility-changing agent **128** (with associated process conditions) is designed to diffuse selectively into overcoat structures **122** such that a width of photoresist structures **109** is designed to be reduced to a final target width at the stages illustrated in FIGS. **1C-1F**.

(119) If, in addition to diffusing into overcoat structures **122**, solubility-changing agent **128** (with associated process conditions) is designed to diffuse laterally into photoresist structures **109'** (FIG. **1I**) such that widths of photoresist structures **109'** will undergo a further width adjustment at the stages illustrated in FIGS. **1I-1J**, then a target depth of lateral diffusion of solubility-changing agent **117** into photoresist structures **109** at FIG. **1C** may be calculated as: $D_{sub.d} =$

$(R_{sub.w1} - R_{sub.wt}) / 2 - D_{sub.sd}$, where $D_{sub.d}$ is the depth of diffusion (whether $D_{sub.d1}$ or $D_{sub.d2}$) being determined for solubility-changing agent **117** into photoresist structures **109** at FIG. **1C**, $R_{sub.wt}$ is the target width for photoresist structures **109''** at FIG. **1J**, and $D_{sub.sd}$ is the depth of expected subsequent diffusion of solubility-changing agent **128** (with associated process conditions) into photoresist structures **109'** (FIG. **1I**), the remaining variables being as previously described. To the extent a 1:1:1:1 feature pitch is targeted, the above formula could be written as $D_{sub.d} = T_{sub.CD} - ((D_{sub.1} + D_{sub.2}) / 2 + D_{sub.sd})$, where $T_{sub.CD}$ is the target CD of patterned features **134**.

(120) For the particular example described in connection with FIGS. 1A-1J, assuming as just an example that a value of D.sub.sd is 20 nm (e.g., based on an assumption that a diffusion rate associated with diffusion of solubility-changing agent **128** into both overcoat structures **122** and photoresist structures **109'** is the same), then a value of D.sub.d is 20 nm (either $((110\text{ nm}-45\text{ nm})/2-12.5\text{ nm})$ or $(45\text{ nm}-(12.5\text{ nm}+12.5\text{ nm})/2+12.5\text{ nm})$).

(121) If, on the other hand, solubility-changing agent **128** (with associated process conditions) is designed to diffuse selectively into overcoat structures **122** such that a width of photoresist structures **109** is designed to be reduced to a final target width (for photoresist structures **109''**) at the stages illustrated in FIGS. 1C-1F, then a target depth of lateral diffusion of solubility-changing agent **117** into photoresist structures **109** at FIG. 1C may be calculated as: $D_{\text{sub.d}} = (R_{\text{sub.w1}} - R_{\text{sub.wt}})/2$, where D.sub.d is the depth of diffusion (whether D.sub.d1 or D.sub.d2) being determined for solubility-changing agent **117** into photoresist structures **109** at FIG. 1C and R.sub.wt is the target width for photoresist structures **109''** at FIG. 1J, the remaining variables being as previously described. To the extent a 1:1:1:1 feature pitch is targeted, the above formula could be written as $D_{\text{sub.d}} = T_{\text{sub.CD}} - ((D_{\text{sub.1}} + D_{\text{sub.2}})/2)$, where T.sub.CD is the target CD of patterned features **134**.

(122) For the particular example described in connection with FIGS. 1A-1J, then a value of D.sub.d is 32.5 nm (either $((110\text{ nm}-45\text{ nm})/2)$ or $(45\text{ nm}-12.5\text{ nm})$).

(123) In the state illustrated in FIG. 1J, patterned features **134** define a pattern that can be transferred to an underlying layer (e.g., intermediate layer **106**). Additionally, when the pattern of patterned features **134** is transferred to the underlying layer, the improved characteristics of patterned features **134**, including potentially sub-resolution features with a reduced or minimized pitch ratio, also may be propagated to the underlying layer.

(124) As illustrated in FIG. 1K, the pattern defined by the combination of overcoat structures **122'**, photoresist structures **109''**, and recesses **124'** (collectively, patterned features **134**) may be transferred to an underlying layer, such as some or all of intermediate layer **106**, thereby potentially transferring the sub-resolution feature widths and feature pitch of the patterned defined by the combination of overcoat structures **122'**, photoresist structures **109''**, and recesses **124'** to the underlying layer. This pattern transfer may be performed using any suitable combination of etch processes, including any suitable wet etch process and dry etch processes. For example, the etch process may include one or more of a liquid etch, a chemical wet etch, a chemical dry etch, a plasma etch, an atomic layer etch, or other suitable etch process. In the illustrated example, transferring the pattern defined by overcoat structures **122'**, photoresist structures **109''**, and recesses **124'** to intermediate layer **106** includes extending recesses **124'** into intermediate layer **106**.

(125) Although the above-described example of patterning process **102** has been described primarily with an example in which line and pitch widths of 45 nm, along with a pitch ratio of 1:1:1:1, are targeted, this disclosure contemplates targeting any suitable line and pitch widths with any suitable pitch ratio.

(126) For brevity and clarity, this description adopts a convention in which elements adhering to the pattern [x02] may be related implementations of a process and/or semiconductor workpiece in certain embodiments. For example, except as otherwise stated or readily apparent, semiconductor workpiece **200** may be similar to semiconductor workpiece **100**, substrate **204** may be similar to substrate **104**, and the like. An analogous convention has also been adopted for other elements as made clear by the use of similar terms in conjunction with the described three-digit numbering system. Through this convention, where applicable, features that have already been described are incorporated by reference without being repeated.

(127) FIG. 2 illustrates a plan view of an example semiconductor workpiece **200** during an example patterning process (e.g., at the state illustrated in FIG. 1J), according to certain embodiments. While recesses **124'** in FIG. 1J extend an entire length of overcoat structures **122'**

and photoresist structures **109''**, with semiconductor workpiece **200**, recesses **224'** extend only a partial length of overcoat structures **222'** and photoresist structures **109''**. For example, overcoat structures **222'** and photoresist structures **209''** have a line length L_i and recesses **124'** have a length S_i (referring to space length), with S_i being less than L_i . In one example, recesses **224'** could be used to form slot contacts within a semiconductor device. Additionally, while recesses **124'** in FIG. **1J** extend an entire length of overcoat structures **122'** and photoresist structures **109''**, a cross-sectional view of semiconductor workpiece **200** taken along line A-A' may appear similar or identical to the cross-sectional view of semiconductor workpiece **100** in FIG. **1J**.

(128) FIG. **3** illustrates an example method **300** for patterning a semiconductor workpiece, according to certain embodiments. Method **300** may be analogous to portions or all of patterning process **102**, and for purposes of describing example method **300**, reference is made primarily to the reference numerals used in connection with FIGS. **1A-1K**. Method **300** also could be used to form a structure similar to semiconductor workpiece **200** of FIG. **2**. Furthermore, aspects of at least FIGS. **1A-1K** and **2** not described in connection with FIG. **3** are incorporated by reference. Method **300**, however, may implement any suitable patterning process.

(129) At step **302**, patterned features **108** are formed from a photoresist layer of a semiconductor workpiece **100**. Patterned features **108** may include photoresist structures **109** formed from the photoresist layer and recesses **110** defined by photoresist structures **109**. In certain embodiments, forming patterned features **108** includes at step **302(a)** depositing the photoresist layer on a semiconductor wafer (semiconductor workpiece **100**) to be patterned by photolithography, at step **302(b)** exposing the photoresist layer to a pattern of actinic radiation, and at step **302(c)** developing the photoresist layer. Following development, remaining portions of the photoresist layer form photoresist structures **109**, which define recesses **110**.

(130) In certain embodiments, a photolithography technology for exposing the photoresist layer to the pattern of actinic radiation includes dry lithography (e.g., using 193 dry lithography), immersion lithography (e.g., using 193 nanometer immersion lithography), i-line lithography (e.g., using 365 nanometer wavelength UV radiation for exposure), H-line lithography (e.g., using 405 nanometer wavelength UV radiation for exposure), EUV lithography, DUV lithography, or any suitable photolithography technology. Additionally, the photolithography technology may be mask-based (e.g., projection lithography), maskless (e.g., e-beam lithography), or another suitable type of lithography.

(131) Recesses **110** may have actual widths ($W_{sub.a}$) that are greater than a target width ($W_{sub.t}$). The actual widths ($W_{sub.a}$) may be determined according to a photolithography technology used to form patterned features **108**. The actual widths ($W_{sub.a}$) may exceed the target width ($W_{sub.t}$) due at least in part to limitations resulting from a wavelength of the photolithography used to form patterned features **108**.

(132) At step **304**, overcoat film **112** is deposited on semiconductor workpiece **100**. Overcoat film **112** fills recesses **110** and covers photoresist structures **109**. In certain embodiments, depositing overcoat film **112** on semiconductor workpiece **100** includes depositing a material of overcoat film **112** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **112** on semiconductor workpiece **100** such that overcoat film **112** fills recesses **110** and covers photoresist structures **109**.

(133) At step **306**, semiconductor workpiece **100** may be baked to form soluble portions **118** of photoresist structures **109**. In certain embodiments, baking semiconductor workpiece **100** to form soluble portions **118** of photoresist structures **109** includes a solubility-changing agent **117** diffusing, in response to heat associated with baking semiconductor workpiece **100**, from overcoat film **112** to perimeter portions of photoresist structures **109**. Solubility-changing agent **117** may modify the perimeter portions of photoresist structures **109** to become soluble for development, thereby forming soluble portions **118** of photoresist structures **109**.

(134) In certain embodiments, solubility-changing agent **117** includes acid and photoresist

structures **109** include an acid-reactive material. In certain embodiments, overcoat film **112** includes a polymer and, as deposited, an agent-generating ingredient for generating solubility-changing agent **117**. For example, the agent-generating ingredient may include a TAG or a PAG. In certain embodiments, the agent-generating ingredient includes a PAG and method **300** further includes exposing, prior to baking semiconductor workpiece **100** at step **306** to form soluble portions **118** of photoresist structures **109**, overcoat film **112** to actinic radiation to cause the PAG in overcoat film **112** to generate solubility-changing agent **117**.

(135) In certain embodiments, baking semiconductor workpiece **100** to form soluble portions **118** of photoresist structures **109** causes solubility-changing agent **117** to diffuse from overcoat film **112** to perimeter portions of photoresist structures **109** up to a target depth. The target depth may be less than or equal to one half of a difference between the first width (e.g., actual width $W_{sub.a}$) and the target width ($W_{sub.t}$). In embodiments in which a width of photoresist structures **109'** is designed to equal a width of photoresist structures **109**, to be formed at steps **312** and **320**, respectively, the target depth may be equal to one half of a difference between the first width (e.g., actual width $W_{sub.a}$) and the target width ($W_{sub.t}$).

(136) At step **308**, overcoat film **112** may be selectively removed.

(137) At step **310**, overcoat film **120** may be deposited on semiconductor workpiece **100**. Overcoat film **120** fills recesses **110** and covers photoresist structures **109**. In certain embodiments, depositing overcoat film **120** on semiconductor workpiece **100** includes depositing a material of overcoat film **120** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **120** on semiconductor workpiece **100** such that overcoat film **120** fills recesses **110** and covers photoresist structures **109**.

(138) At step **312**, semiconductor workpiece **100** is developed to remove portions of overcoat film **120** to reveal and remove soluble portions **118** of photoresist structures **109** to define patterned features **123** that include photoresist structures **108'**, overcoat structures **122** interspersed between photoresist structures **109'**, and recesses **124** defined by photoresist structures **109'** and overcoat structures **122**.

(139) At step **314**, a solubility-changing process is executed to cause overcoat structures **122** to become insoluble for development. In certain embodiments, executing the solubility-changing process to cause overcoat structures **122** to become insoluble for development includes baking semiconductor workpiece **100**. A temperature for baking semiconductor workpiece **100** to cause overcoat structures **122** to become insoluble for development is greater than a temperature for baking semiconductor workpiece **100** to form soluble portions **118** of photoresist structures **109**. In certain embodiments, prior to executing the solubility-changing process at step **314** to cause overcoat structures **122** to become insoluble for development, overcoat film **120** is soluble at a first removal rate in a developer used for developing semiconductor workpiece at step **312** to remove the portions of overcoat film **120** to reveal and remove soluble portions **118** of photoresist structures **109**. Soluble portions **118** of photoresist structures **109** may be soluble at a second removal rate in the developer, the second removal rate being greater than the first removal rate, potentially by a significant amount as described above.

(140) In certain embodiments, executing the solubility-changing process to cause overcoat structures **122** to become insoluble for development includes exposing overcoat structures **122** to actinic radiation.

(141) In certain embodiments, overcoat film **120** includes a polymer and the solubility-changing process causes polymer crosslinking to occur in overcoat structures **122** (made of the material of overcoat film **120**). The polymer crosslinking may render overcoat structures **122** insoluble in a developer for developing semiconductor workpiece to remove an overcoat film **126** and soluble portions **130** of overcoat structures **122** in a subsequent step (see step **320**).

(142) At step **316**, overcoat film **126** may be deposited on semiconductor workpiece **100**. Overcoat film **126** fills recesses **124** and covers photoresist structures **109'** and overcoat structures **122**. In

certain embodiments, depositing overcoat film **126** on semiconductor workpiece **100** includes depositing a material of overcoat film **126** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **126** on semiconductor workpiece **100** such that overcoat film **126** fills recesses **124** and covers photoresist structures **109'** and overcoat structures **122**.

(143) At step **318**, semiconductor workpiece **100** is baked to form soluble portions **130** of overcoat structures **122**. In certain embodiments, baking, subsequent to the polymer crosslinking of step **314**, semiconductor workpiece **100** to form soluble portions **130** of overcoat structures **122** causes perimeter portions to a target depth of overcoat structures **122** to become soluble for development in a developer for developing semiconductor workpiece to remove overcoat film **126** and soluble portions **130** of overcoat structures **122**.

(144) In certain embodiments, baking semiconductor workpiece **100** to form soluble portions **130** of overcoat structures **122** includes a solubility-changing agent **128** diffusing, in response to heat associated with baking semiconductor workpiece **100**, from overcoat film **126** to perimeter portions of overcoat structures **122**. Solubility-changing agent **128** may modify the perimeter portions of overcoat structures **122** to become soluble for development, thereby forming soluble portions **130** of overcoat structures **122**.

(145) In certain embodiments, solubility-changing agent **128** includes acid and overcoat structures **122** include an acid-reactive material. In certain embodiments, overcoat film **126** includes a polymer and, as deposited, an agent-generating ingredient for generating solubility-changing agent **128**. For example, the agent-generating ingredient may include a TAG or a PAG.

(146) In an example in which the agent-generating ingredient includes a PAG, method **300** may further include exposing, prior to baking semiconductor workpiece **100** at step **318** to form soluble portions **130** of overcoat structures **122**, overcoat film **126** to actinic radiation to cause the PAG in overcoat film **126** to generate solubility-changing agent **128**.

(147) In certain embodiments, baking semiconductor workpiece **100** to form soluble portions **130** of overcoat structures **122** causes solubility-changing agent **128** to diffuse from overcoat film **126** to perimeter portions of overcoat structures **122** up to a target depth. The target depth may be less than or equal to one half of a difference between the first width (e.g., actual width $W_{sub.a}$) and the target width ($W_{sub.t}$).

(148) In certain embodiments, portions of photoresist structures **109'** are solubilized and developed at steps **318** and **320**, depending on how removal of certain portions of photoresist structures **109** was biased at steps **306** (diffusion of solubility-changing agent **117** into photoresist structures **109**/depth of soluble portions **118**) and **312** (development to remove soluble portions **118** of photoresist structures **109**). In such an example, baking semiconductor workpiece **100** at step **318** to form soluble portions **130** of overcoat structures **122** further forms soluble portions of photoresist structures **109'** (e.g., by diffusing solubility-changing agent **128** overcoat film **126** into photoresist structures **109'** to form the soluble portions of photoresist structures **109'**) and developing semiconductor workpiece **100** at step **320** (described below) to remove overcoat film **126** and soluble portions **130** of overcoat structures **122** further removes the soluble portions of photoresist structures **109'** to define photoresist structures **109''**. In such an example, the target depth of diffusion of solubility-changing agent **128** from overcoat film **126** to perimeter portions of overcoat structures **122** may be less than one half of a difference between the first width and the target width, and a width of photoresist structures **109''** may be less than a width of photoresist structures **109'** once developed at step **320**.

(149) In certain embodiments, the first widths (e.g., actual width WO exceed the target width ($W_{sub.t}$) by an overage amount ($D_{sub.1}+D_{sub.2}$).

(150) In one example, photoresist structures **109'** and photoresist structures **109''** have a same width, meaning that photoresist structures **109'** are not further solubilized and developed at steps **318** and **320**, respectively. In such an example, baking semiconductor workpiece **100** to form soluble portions **118** of photoresist structures **109** causes solubility-changing agent **117** to diffuse

from overcoat film **112** to the perimeter portions of photoresist structures **109** up to a first diffusion depth, and the second photoresist structures and the third photoresist structures have a same width, and the first diffusion depth may equal the target width ($W_{sub.t}$) minus half the overage amount ($D_{sub.1}+D_{sub.2}$).

(151) In another example, baking semiconductor workpiece **100** to form soluble portions **118** of photoresist structures **109** may cause solubility-changing agent **117** to diffuse from overcoat film **112** to perimeter portions of photoresist structures **109** up to a first diffusion depth. Additionally, in such an example, baking semiconductor workpiece **100** to form soluble portions **130** of overcoat structures **122** may diffuse solubility-changing agent **128** of overcoat film **126** into perimeter portions of overcoat structures **122** by a second diffusion depth. Additionally, in such an example, baking semiconductor workpiece **100** to form soluble portions **130** of overcoat structures **122** further diffuses solubility-changing agent **128** of overcoat film **126** to perimeter portions of photoresist structures **109'** up to a third diffusion depth to form the soluble portions of photoresist structures **109'**. The second and third diffusion depths might or might not be the same. In such an example, the first diffusion depth may equal the target width ($W_{sub.t}$) minus half the overage amount ($D_{sub.1}+D_{sub.2}$) plus a total of the first and second diffusion depths.

(152) At step **320**, semiconductor workpiece **100** is developed to remove overcoat film **126** and soluble portions **130** of overcoat structures **122** to define patterned features **134**. Patterned features **134** include photoresist structures **109''**, overcoat structures **122'** interspersed between photoresist structures **109''**, and recesses **124'** defined by overcoat structures **122'** and photoresist structures **109''**. Overcoat structures **122'** may have the target width ($W_{sub.t}$). In certain embodiments, widths of patterned features **134** are equal and below a resolution capability of a photolithography technology used to form patterned features **108**.

(153) At step **322**, subsequent processing may be performed. For example, patterned features **134** of semiconductor workpiece **100** may be used to form sub-resolution features in an underlying layer (e.g., intermediate layer **106**) of semiconductor workpiece **100**.

(154) Method **300** may then end.

(155) FIG. **4** illustrates an example method **400** for patterning a semiconductor workpiece, according to certain embodiments. Method **400** may be analogous to portions or all of patterning process **102**, and for purposes of describing example method **400**, reference is made primarily to the reference numerals used in connection with FIGS. **1A-1K**. Method **400** also could be used to form a structure similar to semiconductor workpiece **200** of FIG. **2**. Furthermore, aspects of at least FIGS. **1A-1K** and **2** not described in connection with FIG. **4** are incorporated by reference. Method **400**, however, may implement any suitable patterning process.

(156) At step **402**, photoresist structures **109** and recesses **110** may be formed on a semiconductor wafer (e.g., semiconductor workpiece **100**) by photolithography. For example, photoresist structures **109** and recesses **110** may be patterned from a photoresist layer formed on semiconductor workpiece **100**.

(157) Photoresist structures **109** may have widths $R_{sub.w1}$. Recesses **110** may have actual widths ($W_{sub.a}$) that are greater than a target width ($W_{sub.t}$). The actual widths ($W_{sub.a}$) may be determined according to a photolithography technology used to form patterned features **108**. The actual widths ($W_{sub.a}$) may exceed the target width ($W_{sub.t}$) due at least in part to limitations resulting from a wavelength of the photolithography used to form patterned features **108**. That is, a minimum achievable width for actual width $W_{sub.a}$ is determined according to a photolithography technology used for the photolithography.

(158) At step **404**, overcoat film **112** is deposited on semiconductor workpiece **100**. Overcoat film **112** fills recesses **110** and covers photoresist structures **109**. In certain embodiments, depositing overcoat film **112** on semiconductor workpiece **100** includes depositing a material of overcoat film **112** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **112** on semiconductor workpiece **100** such that overcoat film **112** fills recesses **110** and covers

photoresist structures **109**.

(159) At step **406**, using overcoat film **112**, soluble portions **118** of photoresist structures **109** may be formed. For example, soluble portions **118** of photoresist structures **109** may be formed using a suitable combination of exposing semiconductor workpiece **100** to actinic radiation and/or baking semiconductor workpiece **100** to cause a solubility-changing agent **117** (e.g., acid) to diffuse into and solubilize portions of photoresist structures **109** to form soluble portions **118**.

(160) At step **408**, overcoat film **112** may be selectively removed.

(161) At step **410**, overcoat film **120** may be deposited on semiconductor workpiece **100**. Overcoat film **120** fills recesses **110** and covers photoresist structures **109**. In certain embodiments, depositing overcoat film **120** on semiconductor workpiece **100** includes depositing a material of overcoat film **120** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **120** on semiconductor workpiece **100** such that overcoat film **120** fills recesses **110** and covers photoresist structures **109**.

(162) At step **412**, portions of overcoat film **120** and soluble portions **118** of photoresist structures **109** are removed to define photoresist structures **109'**, overcoat structures **122** of overcoat film **120** and occupying recesses **110**, and recesses **124** in regions previously occupied by soluble portions **118** of photoresist structures **109**. Photoresist structures **109'** have a width $R_{sub.w2}$ that is less than the width $R_{sub.w1}$ of photoresist structures **109**. Overcoat structures **122** have the actual width $W_{sub.a}$ of now-filled recesses **110**. Recesses **124** have a width ($D_{sub.d1}$ or $D_{sub.d2}$) that is less than the target width ($W_{sub.t}$).

(163) At step **414**, overcoat structures **122** are modified to become insoluble for development. In certain embodiments, overcoat film **120** includes a polymer resin and modifying overcoat structures **122** to become insoluble for development includes causing, in response to an activation trigger, a polymer crosslinking reaction to occur overcoat film **120** (e.g., overcoat structures **122** formed from overcoat film **120**) that renders overcoat film **120** (e.g., overcoat structures **122** formed from overcoat film **120**) insoluble for development in a developer used for selectively removing an overcoat film **126** and soluble portions **130** of overcoat structures **122** in a subsequent step of method **400**. In certain embodiments, the activation trigger includes heating semiconductor workpiece **100** and/or exposing overcoat film **120** (e.g., overcoat structures **122** formed from overcoat film **120**) to actinic radiation.

(164) At step **416**, overcoat film **126** may be deposited on semiconductor workpiece **100**. Overcoat film **126** fills recesses **124** and covers photoresist structures **109'** and overcoat structures **122**. In certain embodiments, depositing overcoat film **126** on semiconductor workpiece **100** includes depositing a material of overcoat film **126** by spin-coating (e.g., using spin-on deposition technique **114**) the material of overcoat film **126** on semiconductor workpiece **100** such that overcoat film **126** fills recesses **124** and covers photoresist structures **109'** and overcoat structures **122**.

(165) At step **418**, using overcoat film **126**, soluble portions **130** of overcoat structures **122** may be formed. For example, soluble portions **130** of overcoat structures **122** may be formed using a suitable combination of exposing semiconductor workpiece **100** to actinic radiation and/or baking semiconductor workpiece **100** to cause a solubility-changing agent **128** (e.g., acid) to diffuse into and solubilize portions of overcoat structures **122** to form soluble portions **130**. In certain embodiments, lateral depths of soluble portions **130** of overcoat structures **122** equal one half a difference between the target width $W_{sub.t}$ and the actual width $W_{sub.a}$.

(166) At step **420**, overcoat film **126** and soluble portions **130** of overcoat structures **122** are selectively removed to define photoresist structures **109''**, overcoat structures **122'** interspersed between photoresist structures **109''**, and recesses **124'** defined by photoresist structures **109''** and overcoat structures **122'**. Following a width reduction associated with the acid diffusion process of step **506** during which portions of overcoat structures **122** have been selectively removed to form overcoat structures **122'**, overcoat structures **122'** have the target width $W_{sub.t}$, and recesses **124'** have a width ($S_{sub.w}$), which is greater than a width ($D_{sub.d1}$ or $D_{sub.d2}$) of recesses **124**.

Width S.sub.w may be the target width (W.sub.t).

(167) Photoresist structures **109''** may have a width R.sub.w2, which might be the same or less than the width R.sub.w2 of photoresist structures **109'**, depending on whether the acid diffusion process of step **506** further reduces a width of photoresist structures **109'** to form photoresist structures **109''**. In certain embodiments, the width R.sub.w2 of photoresist structures **109''** is the same as the width R.sub.w2 of photoresist structures **109'**, and in such an example, a lateral depth of soluble portions **118** of photoresist structures **109** at step **406** equals one half a difference between width R.sub.w1 of photoresist structures **109** and width R.sub.w2, of photoresist structures **109'/109''**. In certain other embodiments, the width R.sub.w2 of photoresist structures **109''** is less than the width R.sub.w2 of photoresist structures **109'**, and in such an example, step **418** may further include forming, using overcoat film **126**, soluble portions of photoresist structures **109'** and step **420** may further include selectively removing, when selectively removing overcoat film **126** and soluble portions **130** of overcoat structures **122**, the soluble portions of photoresist structures **109'** to define photoresist structures **109''**. Widths R.sub.w2 of photoresist structures **109''** may equal target width W.sub.t.

(168) In certain embodiments, widths R.sub.w2 of photoresist structures **109''** equal target width W.sub.t, widths of overcoat structures **122'** equal target width W.sub.t, and widths S.sub.w of recesses **124'** equal target width W.sub.t, and a 1:1:1:1 line-space-line-space pitch ratio is defined. In certain embodiments, the target width W.sub.t is less than a minimum achievable width associated with the photolithography technology used at step **402** to form photoresist structures **109** and recesses **110**.

(169) At step **422**, subsequent processing may be performed. For example, patterned features **134** of semiconductor workpiece **100** may be used to form sub-resolution features in an underlying layer (e.g., intermediate layer **106**) of semiconductor workpiece **100**.

(170) Method **400** may then end.

(171) FIG. 5 illustrates an example method **500** for patterning a semiconductor workpiece, according to certain embodiments. Method **500** may be analogous to portions or all of patterning process **102**, and for purposes of describing example method **500**, reference is made primarily to the reference numerals used in connection with FIGS. 1A-1K. Method **500** also could be used to form a structure similar to semiconductor workpiece **200** of FIG. 2. Furthermore, aspects of at least FIGS. 1A-1K and 2 not described in connection with FIG. 5 are incorporated by reference. Method **500**, however, may implement any suitable patterning process.

(172) At step **502**, patterned features **108** may be formed on a semiconductor wafer (e.g., semiconductor workpiece **100**) by photolithography. Patterned features **108** may include photoresist structures **109** and recesses **110** defined by photoresist structures **109**. For example, patterned features **108** may be patterned from a photoresist layer formed on semiconductor workpiece **100**.

(173) Photoresist structures **109** may have widths R.sub.w1. Recesses **110** may have actual widths (W.sub.a) that are greater than a target width (W.sub.t). The actual widths (W.sub.a) may be determined according to a photolithography technology used to form patterned features **108**. The actual widths (W.sub.a) may exceed the target width (W.sub.t) due at least in part to limitations resulting from a wavelength of the photolithography used to form patterned features **108**. That is, a minimum achievable width for actual width W.sub.a is determined according to a photolithography technology used for the photolithography.

(174) At step **504**, using an anti-spacer patterning process, patterned features **123** may be formed on semiconductor workpiece **100**. Patterned features **123** may include photoresist structures **109'**, overcoat structures **122** interspersed between photoresist structures **109'**, and recesses **124** defined by photoresist structures **109'** and overcoat structures **122**. Photoresist structures **109'** have a width R.sub.w2 that is less than the width R.sub.w1 of photoresist structures **109**. Overcoat structures **122** have the actual width W.sub.a of now-filled recesses **110**. Recesses **124** have a width (D.sub.d1 or

D.sub.d2) that is less than the target width (W.sub.t). In certain embodiments, the anti-spacer process corresponds to some or all of the steps of patterning process **102** associated with FIGS. **1A-1F**, some or all of steps **302** through **312** of method **300** from FIG. **3**, or some or all of steps **402-412** of method **400** from FIG. **4**.

(175) At step **506**, using an acid diffusion process, patterned features **134** may be formed on semiconductor workpiece **100**. Patterned features **134** may include photoresist structures **109''**, overcoat structures **122'** interspersed between photoresist structures **109''**, and recesses **124'** defined by photoresist structures **109''** and overcoat structures **122'**. Photoresist structures **109''** may have a width R.sub.w2, which might be the same or less than the width R.sub.w2 of photoresist structures **109'**, depending on whether the acid diffusion process of step **506** further reduces a width of photoresist structures **109'** to form photoresist structures **109''**. Following a width reduction associated with the acid diffusion process of step **506** during which portions of overcoat structures **122** have been selectively removed to form overcoat structures **122'**, overcoat structures **122'** have the target width W.sub.t, and recesses **124'** have a width (S.sub.w), which is greater than a width (D.sub.d1 or D.sub.d2) of recesses **124**. Width S.sub.w may be the target width (W.sub.t).

(176) In certain embodiments, the acid diffusion process (which for purposes of this example may include an associated development process) corresponds to some or all of the steps of patterning process **102** associated with FIGS. **1H-1J**, some or all of steps **316** through **320** of method **300** from FIG. **3**, or some or all of steps **416-420** of method **400** from FIG. **4**. In certain embodiments, prior to or as part of the acid diffusion process of step **506**, a solubility-changing process may be executed to cause overcoat structures **122** to become insoluble for development.

(177) At step **508**, subsequent processing may be performed. For example, patterned features **134** of semiconductor workpiece **100** may be used to form sub-resolution features in an underlying layer (e.g., intermediate layer **106**) of semiconductor workpiece **100**.

(178) Method **500** may then end.

(179) Methods **300**, **400**, and **500** may be combined with each other or other methods and performed using the systems and apparatuses described herein. Although shown in a logical order, the arrangement and numbering of the steps of methods **300**, **400**, and **500** are not intended to be limited. The steps of methods **300**, **400**, and **500** may be performed in any suitable order or concurrently with one another as may be apparent to a person of skill in the art.

(180) FIGS. **6-7** illustrate example processing tools that may be used, along or in combination, to implement certain embodiments of this disclosure.

(181) FIG. **6** illustrates a block diagram of an example lithography system **600**, according to certain embodiments. Lithography system **600** is just one example of a lithography system that may be used with certain embodiments of this disclosure. In the illustrated example, lithography system **600** includes a track system **602** and a projection scanner **604**. In certain embodiments, lithography system **600** is generally configured for performing certain embodiments of patterning process **102** and/or methods **300/400/500**.

(182) Scanner **604** may be configured to perform an exposure phase of a photolithography process. In certain embodiments, scanner **604** is a combination of an optical and mechanical system to scan an optical image of a pattern printed on a photomask onto the surface of a wafer (e.g., semiconductor workpiece **100**) coated with resist (e.g., a photoresist layer from which photoresist structures **109** are formed). After scanning the pattern once, scanner **604** may be operated to step to an adjacent location on the same wafer where the scan is repeated to form another copy of the pattern. In this manner, the photoresist layer is exposed to multiple copies of the pattern arranged in a rectangular matrix on the surface of the wafer. Scanner **604** may be used as part of the photolithography process to form patterned features **108**.

(183) Track system **602** includes a series of process modules assembled to allow potentially sequential execution of processes for the lithography process prior to the exposure and after the exposure step performed by scanner **604**. Track system **602** provides the material processes such as

coating the wafer with photoresist, baking the photoresist, and developing the photoresist after exposure. In the illustrated example, the process modules of track system **602** include a spin-coating module **606**, a pre-exposure bake module **608**, a solvent wash module **610**, a post-exposure bake module **612**, a developing module **614**, a spin-coating module **616**, a bake module **618**, a solvent wash module **620**, a spin-coating module **622**, a developing module **624**, a bake module **626**, a spin-coating module **628**, a bake module **630**, and a developing module **632**. These modules may correspond to the steps of patterning process **102** described above with reference to FIGS. **1A-1J** and/or method **300/400/500** described above with reference to FIGS. **3-5**. Spin-coating modules **606**, **616**, **622**, and **628** include a spin-coater, an example of which is described below with reference to FIG. **7**. Photoresist materials, overcoat materials, and solvents are connected from a liquid supply system to suitable processing modules (e.g., spin-coating modules **606**, **616**, **622**, and **628**, developing modules **614**, **624**, and **632**, etc.) via pipelines, filters, valves, and pumps.

(184) In addition to process modules, track system **602** could include an imaging module and could also include an inspection and metrology (IM) module, along with any other suitable module. For example, to the extent agent-generating ingredients in the form of PAGs are included in one or more overcoat films, associated irradiation modules (e.g., for exposing a semiconductor workpiece to flood radiation) may be inserted at appropriate locations along the track.

(185) Lithography system **600** may include a transfer system to move a wafer (e.g., a semiconductor workpiece) from module-to-module of track system **602**, as well as from track system **602** to projection scanner **604** (which may be considered “off track”) and from projection scanner **604** back to track system **602**.

(186) FIG. **7** illustrates an example liquid-based spin-on deposition system **700**, according to certain embodiments. For example, liquid-based spin-on deposition system **700** may be used to process any of the described semiconductor workpieces to deposit any of the photoresist layers, barrier layers, photoresist formulas, overcoat films or other suitable materials described in this disclosure. In certain embodiments, spin-on deposition system **700** may be a semi-closed spin-on deposition system used for coating substrates (wafers) with a desired layer. The semi-closed configuration may allow fume control and minimize exhaust volume.

(187) In the illustrated example, spin-on deposition system **700** includes a process chamber **702** that includes a substrate holder **704** for supporting, heating, and rotating (spinning) a substrate **706** (which may include any of the semiconductor workpieces described in this disclosure at appropriate stages of processing), a rotating apparatus **708** (e.g., a motor), and a liquid delivery nozzle **710** configured for providing a processing liquid **712** to an upper surface of substrate **706**. Liquid supply systems **714**, **716**, and **718** supply different processing liquids to liquid delivery nozzle **710**. For depositing a photoresist, the different processing liquids can include, for example, a first reactant in a first liquid, a second reactant in a second liquid, and a rinsing liquid. In certain embodiments, spin-on deposition system **700** includes additional liquid delivery nozzles for providing different liquids to substrate **706**. Example rotating speeds can be between about 500 rpm and about 1500 rpm, for example 1000 rpm, during exposure of an upper surface of substrate **706** to processing liquid **712**.

(188) Spin-on deposition system **700** may include a controller **720** that can be coupled to and control process chamber **702**; liquid supply systems **714**, **716**, and **718**; liquid delivery nozzle **710**; rotating apparatus **708**, mechanism for heating substrate holder **704**. Substrate **706** may be under an inert atmosphere during film deposition. Spin-on deposition system **700** may be configured to process substrates **706** of any suitable size.

(189) Certain embodiments may provide none, some, or all of the following technical advantages. Other advantages may be described throughout this disclosure or otherwise be apparent from this disclosure to one of skill in the art.

(190) Certain embodiments may allow access to CDs that extend beyond CDs achievable using a particular photolithography technology. Such critical dimensions that exceed a CD that is directly

achievable with a particular photolithography technology and its associated wavelength may be referred to as sub-resolution features. For example, certain embodiments of this disclosure may allow 248 nm lithography to access dimensions achievable using 193 nm dry lithography and/or potentially beyond. As another example, certain embodiments of this disclosure may allow 193 nm dry lithography to access dimensions achievable using 193 nm immersion lithography and/or potentially beyond. As another example, certain embodiments of this disclosure may allow 193 nm immersion lithography to access dimensions achievable using EUV lithography and/or potentially beyond. As another example, certain embodiments of this disclosure may allow 193 nm dry lithography to access dimensions achievable using 193 nm immersion lithography and/or potentially beyond.

(191) Furthermore, in addition to allowing certain sub-resolution feature sizes to be achieved, certain embodiments are able to achieve target pitch ratios, which may increase feature density on a semiconductor workpiece. In certain embodiments, a 1:1:1:1 line-space-line-space pitch ratio may be achieved. Thus, certain embodiments modify an anti-spacer patterning process to allow a narrow pitch density to be achieved that exceeds a pitch density that can be achieved using the photolithography technology being used as part of the anti-spacer process or using the anti-spacer process alone.

(192) Thus, certain embodiments may allow manufacturers (e.g., semiconductor fabricators) to use older and/or less expensive photolithography technologies (e.g., 193 nm dry photolithography) without investing in expensive newer photolithography technology to achieve sub-resolution feature sizes and reduced pitch ratios. Additionally or alternatively, even with expensive newer technology, certain embodiments may allow manufacturers (e.g., semiconductor fabricators) to achieve feature sizes and pitch ratios even beyond those directly achievable with the newer technology. This cost reduction may reduce a barrier to entry into certain node sizes and/or types of semiconductor devices.

(193) Certain embodiments provide a track-based solution that can be incorporated into a photolithography track, which may facilitate process integration.

(194) Certain embodiments provide a time-efficient solution to reducing or minimizing sub-resolution feature pitch ratio. For example, in certain embodiments the diffusion/deprotection process (e.g., to achieve a 45 nm feature size) can be accomplished in two minutes or less, and potential less than ninety seconds, which provides a time-efficient solution, particularly when compared to other possible processes that may involve lengthy layer-growing processes (e.g., at angstroms per minute).

(195) Example embodiments of this disclosure are summarized here. Other embodiments can also be understood from the entirety of the specification as well as the claims filed herein.

(196) Example 1. A method includes depositing a first overcoat film on a semiconductor wafer that includes first patterned features of a photoresist layer, the first patterned features include first photoresist structures and first recesses defined by the first photoresist structures. The first overcoat film fills the first recesses and covers the first photoresist structures. The first recesses have first widths that are greater than a target width. The method includes baking the semiconductor wafer to form soluble portions of the first photoresist structures, selectively removing the first overcoat film, and depositing a second overcoat film that fills the first recesses and covers the first photoresist structures. The method includes developing the semiconductor wafer to remove portions of the second overcoat film to reveal and remove the soluble portions of the first photoresist structures to define second patterned features that include second photoresist structures, first overcoat structures interspersed between the second photoresist structures, and second recesses defined by the second photoresist structures and the first overcoat structures. The method includes executing a solubility-changing process to cause the first overcoat structures to become insoluble for development, depositing a third overcoat film that fills the second recesses and covers the second photoresist structures and the first overcoat structures, and baking the semiconductor wafer to form soluble

portions of the first overcoat structures. The method includes developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures to define third patterned features that include third photoresist structures, second overcoat structures interspersed between the third photoresist structures, and third recesses defined by the second overcoat structures and the third photoresist structures. The second overcoat structures have the target width.

(197) Example 2. The method of Example 1, where baking the semiconductor wafer to form soluble portions of the first photoresist structures includes a solubility-changing agent diffusing, in response to heat associated with baking the semiconductor wafer, from the first overcoat film to perimeter portions of the first photoresist structures, the solubility-changing agent modifying the perimeter portions of the first photoresist structures to become soluble for development, thereby forming the soluble portions of the first photoresist structures.

(198) Example 3. The method of any one of Examples 1-2, where the solubility-changing agent includes acid and the first photoresist structures include an acid-reactive material.

(199) Example 4. The method of any one of Examples 1-3, where the first overcoat film includes a polymer and an agent-generating ingredient for generating the solubility-changing agent, the agent-generating ingredient including a TAG or a PAG.

(200) Example 5. The method of any one of Examples 1-4, where the agent-generating ingredient includes a PAG and the method further includes exposing, prior to baking the semiconductor wafer to form soluble portions of the first photoresist structures, the first overcoat film to actinic radiation to cause the PAG in the first overcoat film to generate the solubility-changing agent.

(201) Example 6. The method of any one of Examples 1-5, where baking the semiconductor wafer to form the soluble portions of the first photoresist structures causes the solubility-changing agent to diffuse from the first overcoat film to the perimeter portions of the first photoresist structures up to a target depth, the target depth being less than or equal to one half of a difference between the first width and the target width.

(202) Example 7. The method of any one of Examples 1-6, where the target depth is equal to one half of a difference between the first width and the target width, and where a width of the second photoresist structures equals a width of the third photoresist structures.

(203) Example 8. The method of any one of Examples 1-6, where: the target depth is less than one half of a difference between the first width and the target width; baking the semiconductor wafer to form the soluble portions of the first overcoat structures further forms soluble portions of the second photoresist structures; developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures further removes the soluble portions of the second photoresist structures to define the third photoresist structures; and a width of the third photoresist structures is less than a width of the second photoresist structures.

(204) Example 9. The method of any one of Examples 1-8, where: executing the solubility-changing process to cause the first overcoat structures to become insoluble for development includes baking the semiconductor wafer; and a temperature for baking the semiconductor wafer to cause the first overcoat structures to become insoluble for development is greater than a temperature for baking the semiconductor wafer to form the soluble portions of the first photoresist structures.

(205) Example 10. The method of any one of Examples 1-9, where, prior to executing the solubility-changing process to cause the first overcoat structures to become insoluble for development, the second overcoat film is soluble at a first removal rate in a developer used for developing the semiconductor wafer to remove the portions of the second overcoat film to reveal and remove the soluble portions of the first photoresist structures, the soluble portions of the first photoresist structures being soluble at a second removal rate in the developer, the second removal rate being greater than the first removal rate.

(206) Example 11. The method of any one of Examples 1-10, where executing the solubility-

changing process to cause the first overcoat structures to become insoluble for development includes exposing the first overcoat structures to actinic radiation.

(207) Example 12. The method of any one of Examples 1-11, where the second overcoat film includes a polymer and the solubility-changing process causes polymer crosslinking to occur in the second overcoat structures, the polymer crosslinking rendering the second overcoat structures insoluble in a developer for developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures.

(208) Example 13. The method of any one of Examples 1-12, where baking, subsequent to the polymer crosslinking, the semiconductor wafer to form the soluble portions of the first overcoat structures causes perimeter portions to a target depth of the first overcoat structures to become soluble for development in a developer for developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures.

(209) Example 14. The method of any one of Examples 1-13, where baking the semiconductor wafer to form soluble portions of the first overcoat structures includes a solubility-changing agent diffusing, in response to heat associated with baking the semiconductor wafer, from the third overcoat film to perimeter portions of the first overcoat structures, the solubility-changing agent modifying the perimeter portions of the first overcoat structures to become soluble for development, thereby forming the soluble portions of the first overcoat structures.

(210) Example 15. The method of any one of Examples 1-14, where the solubility-changing agent includes acid and the first overcoat structures include an acid-reactive material.

(211) Example 16. The method of any one of Examples 1-15, where the third overcoat film includes a polymer and an agent-generating ingredient for generating the solubility-changing agent, the agent-generating ingredient including a TAG or a PAG.

(212) Example 17. The method of any one of Examples 1-16, where the agent-generating ingredient includes a PAG and the method further includes exposing, prior to baking the semiconductor wafer to form soluble portions of the first overcoat structures, the third overcoat film to actinic radiation to cause the photoacid generator in the third overcoat film to generate the solubility-changing agent.

(213) Example 18. The method of any one of Examples 1-17, where baking the semiconductor wafer to form the soluble portions of the first overcoat structures causes the solubility-changing agent to diffuse from the third overcoat film to the perimeter portions of the first overcoat structures up to a target depth, the target depth being less than or equal to one half of a difference between the first width and the target width.

(214) Example 19. The method of any one of Examples 1-18, where: the target depth is less than one half of a difference between the first width and the target width; baking the semiconductor wafer to form the soluble portions of the first overcoat structures further forms soluble portions of the second photoresist structures; developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures further removes the soluble portions of the second photoresist structures to define the third photoresist structures; and a width of the third photoresist structures is less than a width of the second photoresist structures.

(215) Example 20. The method of any one of Examples 1-19, where: baking the semiconductor wafer to form the soluble portions of the first overcoat structures diffuses a first solubility-changing agent of the third overcoat film into the second photoresist structures to form soluble portions of the second photoresist structures; and developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures further removes the soluble portions of the first photoresist structures to define the third photoresist structures.

(216) Example 21. The method of any one of Examples 1-20, where: the first widths exceed the target width by an overage amount; baking the semiconductor wafer to form the soluble portions of the first photoresist structures causes a second solubility-changing agent to diffuse from the first overcoat film to perimeter portions of the first photoresist structures up to a first diffusion depth;

baking the semiconductor wafer to form the soluble portions of the first overcoat structures diffuses the first solubility-changing agent of the third overcoat film into perimeter portions of the first overcoat structures by a second diffusion depth; baking the semiconductor wafer to form the soluble portions of the first overcoat structures further diffuses the first solubility-changing agent of the third overcoat film to perimeter portions of the second photoresist structures up to a third diffusion depth to form the soluble portions of the second photoresist structures; and the first diffusion depth equals the target width minus half the overage amount plus a total of the second diffusion depth and the third diffusion depth.

(217) Example 22. The method of any one of Examples 1-21, where: the first widths exceed the target width by an overage amount; baking the semiconductor wafer to form the soluble portions of the first photoresist structures causes a solubility-changing agent to diffuse from the first overcoat film to perimeter portions of the first photoresist structures up to a first diffusion depth; the second photoresist structures and the third photoresist structures have a same width; and the first diffusion depth equals the target width minus half the overage amount.

(218) Example 23. The method of any one of Examples 1-23, further including forming the first patterned features on the semiconductor wafer, where forming the first patterned features includes: depositing the photoresist layer on a semiconductor wafer to be patterned by photolithography; exposing the photoresist layer to a pattern of actinic radiation; and developing the photoresist layer, remaining portions of the photoresist layer forming the first photoresist structures and defining the first recesses.

(219) Example 24. The method of any one of Examples 1-23, where the first widths are determined according to a photolithography technology used to form the first patterned features, and where the target width is less than the first widths.

(220) Example 25. The method of any one of Examples 1-24, where widths of the third patterned features are equal and below a resolution capability of a photolithography technology used to form the first patterned features.

(221) Example 26. The method of any one of Examples 1-25, where one or more of a photoresist layer from which the first photoresist structures are formed, the first overcoat film, the second overcoat film, or the third overcoat film are deposited by spin-coating.

(222) Example 27. The method of any one of Examples 1-26, further including using the third patterned features to form sub-resolution features in an underlying layer of the semiconductor wafer.

(223) Example 28. A method includes forming, on a semiconductor wafer by photolithography, first photoresist structures having a first width and first recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width. The method includes depositing a first overcoat film; forming, using the first overcoat film, soluble portions of the first photoresist structures; selectively removing the first overcoat film; and depositing a second overcoat film. The method includes removing portions of the second overcoat film and the soluble portions of the first photoresist structures to define second photoresist structures having a third width less than the first width, first overcoat structures of the second overcoat film, and second recesses in regions previously occupied by the soluble portions of the first photoresist structures. The first overcoat structures have the second width, and the second recesses have a fourth width less than the target width. The method includes modifying the first overcoat structures to become insoluble for development; depositing a third overcoat film; forming, using the third overcoat film, soluble portions of the first overcoat structures; and selectively removing the third overcoat film and the soluble portions of the first overcoat structures to define third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having a sixth width equal to the target width, and third recesses defined by the third photoresist structures and the second overcoat structures and having a seventh width greater than the fourth width.

(224) Example 29. The method of Example 28, where the fifth width equals the third width, and where a lateral depth of the soluble portions of the first photoresist structures equals one half a difference between the first width and the third width.

(225) Example 30. The method of Example 28, where the fifth width is less than the third width, and where the method further includes: forming, using the third overcoat film, soluble portions of the second photoresist structures; and selectively removing, when selectively removing the third overcoat film and the soluble portions of the first overcoat structures, the soluble portions of the second photoresist structures to define the third photoresist structures.

(226) Example 31. The method of any one of Examples 28-30, where the seventh width equals the target width.

(227) Example 32. The method of any one of Examples 28-31, where the fifth width equals the target width.

(228) Example 33. The method of any one of Examples 28-32, where the fifth, sixth, and seventh widths equal the target width and define a 1:1:1:1 line-space-line-space pitch ratio.

(229) Example 34. The method of any one of Examples 28-33, where the second overcoat film includes a polymer resin and modifying the first overcoat structures to become insoluble for development includes causing, in response to an activation trigger, a polymer crosslinking reaction to occur in the second overcoat film that renders the first overcoat film insoluble for development in a developer used for selectively removing the third overcoat film and the soluble portions of the first overcoat structures.

(230) Example 35. The method of any one of Examples 28-34, where the activation trigger includes heating the semiconductor wafer or exposing the second overcoat film to actinic radiation.

(231) Example 36. The method of any one of Examples 28-35, where a lateral depth of the soluble portions of the first overcoat structures equals one half a difference between the target width and the second width.

(232) Example 37. The method of any one of Examples 28-36, where: a minimum achievable width for the second width is determined according to a photolithography technology used for the photolithography; and the target width is less than the minimum achievable width.

(233) Example 38. A method includes forming, by photolithography on a semiconductor wafer, first patterned features including first photoresist structures having a first width and first recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width. The method includes forming, using an anti-spacer patterning process, second patterned features including second photoresist structures having a third width less than the first width, first overcoat structures interspersed between the second photoresist structures and having the second width, and second recesses defined by the second photoresist structures and the first overcoat structures and having a fourth width less than the target width. The method includes forming, using an acid diffusion process, third patterned features that include third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having the target width, and third recesses defined by the third photoresist structures and the second overcoat structures and having a sixth width greater than the fourth width, portions of the first overcoat structures having been selectively removed using the acid diffusion process to form the second overcoat structures.

(234) In the preceding description, specific details have been set forth, such as a particular geometry of a processing system and descriptions of various components and processes used therein. It should be understood, however, that techniques herein may be practiced in other embodiments that depart from these specific details, and that such details are for purposes of explanation and not limitation. Embodiments disclosed herein have been described with reference to the accompanying drawings. Similarly, for purposes of explanation, specific numbers, materials, and configurations have been set forth in order to provide a thorough understanding. Nevertheless, embodiments may be practiced without such specific details. Components having substantially the

same functional constructions are denoted by like reference characters, and thus any redundant descriptions may be omitted.

(235) The order of discussion of the different steps as described herein has been presented for clarity sake. In general, these steps can be performed in any suitable order. Additionally, although each of the different features, techniques, configurations, etc. herein may be discussed in different places of this disclosure, it is intended that each of the concepts can be executed independently of each other or in combination with each other. Accordingly, the present disclosure can be embodied and viewed in many different ways.

(236) “Substrate,” “target substrate,” “structure,” or “device” as used herein generically refers to an object being processed in accordance with the disclosure, and may include any material portion or structure of a device, particularly a semiconductor or other electronics device, and may, for example, be a base substrate structure, such as a semiconductor wafer, reticle, or a layer on or overlying a base substrate structure such as a thin film. Thus, substrate, structure, or device is not limited to any particular base structure, underlying layer or overlying layer, patterned or unpatterned, but rather, is contemplated to include any such layer or base structure, and any combination of layers and/or base structures. The description may reference particular types of substrates, structures, or devices, but this is for illustrative purposes only.

(237) Although this disclosure describes particular process steps as occurring in a particular order, this disclosure contemplates the process steps occurring in any suitable order. While this disclosure has been described with reference to illustrative embodiments, this description is not intended to be construed in a limiting sense. Various modifications and combinations of the illustrative embodiments, as well as other embodiments of the disclosure, will be apparent to persons skilled in the art upon reference to the description. It is therefore intended that the appended claims encompass any such modifications or embodiments.

Claims

1. A method, comprising: depositing a first overcoat film on a semiconductor wafer, the semiconductor wafer comprising first patterned features of a photoresist layer, the first patterned features comprising first photoresist structures and first recesses defined by the first photoresist structures, the first overcoat film filling the first recesses and covering the first photoresist structures, the first recesses having first widths that are greater than a target width; baking the semiconductor wafer to form soluble portions of the first photoresist structures; selectively removing the first overcoat film; depositing a second overcoat film that fills the first recesses and covers the first photoresist structures; developing the semiconductor wafer to remove portions of the second overcoat film to reveal and remove the soluble portions of the first photoresist structures to define second patterned features that comprise second photoresist structures, first overcoat structures interspersed between the second photoresist structures, and second recesses defined by the second photoresist structures and the first overcoat structures; executing a solubility-changing process to cause the first overcoat structures to become insoluble for development; depositing a third overcoat film that fills the second recesses and covers the second photoresist structures and the first overcoat structures; baking the semiconductor wafer to form soluble portions of the first overcoat structures; and developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures to define third patterned features that comprise third photoresist structures, second overcoat structures interspersed between the third photoresist structures, and third recesses defined by the second overcoat structures and the third photoresist structures, wherein the second overcoat structures have the target width.

2. The method of claim 1, wherein baking the semiconductor wafer to form soluble portions of the first photoresist structures comprises a solubility-changing agent diffusing, in response to heat associated with baking the semiconductor wafer, from the first overcoat film to perimeter portions

of the first photoresist structures up to a target depth, the solubility-changing agent modifying the perimeter portions of the first photoresist structures to become soluble for development, thereby forming the soluble portions of the first photoresist structures, the target depth being less than or equal to one half of a difference between the first width and the target width.

3. The method of claim 2, wherein: the solubility-changing agent comprises acid; the first photoresist structures comprise an acid-reactive material and the first overcoat film comprises: a polymer; and an agent-generating ingredient for generating the solubility-changing agent, the agent-generating ingredient comprising a thermal-acid generator or a photoacid generator.

4. The method of claim 1, wherein: executing the solubility-changing process to cause the first overcoat structures to become insoluble for development comprises baking the semiconductor wafer; and a temperature for baking the semiconductor wafer to cause the first overcoat structures to become insoluble for development is greater than a temperature for baking the semiconductor wafer to form the soluble portions of the first photoresist structures.

5. The method of claim 1, wherein: the second overcoat film comprises a polymer; and the solubility-changing process causes polymer crosslinking to occur in the second overcoat structures, the polymer crosslinking rendering the second overcoat structures insoluble in a developer for developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures.

6. The method of claim 1, wherein baking the semiconductor wafer to form soluble portions of the first overcoat structures comprises a solubility-changing agent diffusing, in response to heat associated with baking the semiconductor wafer, from the third overcoat film to perimeter portions of the first overcoat structures up to a target depth, the solubility-changing agent modifying the perimeter portions of the first overcoat structures to become soluble for development, thereby forming the soluble portions of the first overcoat structures, the target depth being less than or equal to one half of a difference between the first width and the target width.

7. The method of claim 6, wherein: the solubility-changing agent comprises acid; and the first overcoat structures comprise an acid-reactive material the third overcoat film comprises: a polymer; and an agent-generating ingredient for generating the solubility-changing agent, the agent-generating ingredient comprising a thermal-acid generator or a photoacid generator.

8. The method of claim 1, wherein: baking the semiconductor wafer to form the soluble portions of the first overcoat structures diffuses a first solubility-changing agent of the third overcoat film into the second photoresist structures to form soluble portions of the second photoresist structures; and developing the semiconductor wafer to remove the third overcoat film and the soluble portions of the first overcoat structures further removes the soluble portions of the first photoresist structures to define the third photoresist structures.

9. The method of claim 8, wherein: the first widths exceed the target width by an overage amount; baking the semiconductor wafer to form the soluble portions of the first photoresist structures causes a second solubility-changing agent to diffuse from the first overcoat film to perimeter portions of the first photoresist structures up to a first diffusion depth; baking the semiconductor wafer to form the soluble portions of the first overcoat structures diffuses the first solubility-changing agent of the third overcoat film into perimeter portions of the first overcoat structures by a second diffusion depth; baking the semiconductor wafer to form the soluble portions of the first overcoat structures further diffuses the first solubility-changing agent of the third overcoat film to perimeter portions of the second photoresist structures up to a third diffusion depth to form the soluble portions of the second photoresist structures; and the first diffusion depth equals the target width minus half the overage amount plus a total of the second diffusion depth and the third diffusion depth.

10. The method of claim 1, wherein: the first widths exceed the target width by an overage amount; baking the semiconductor wafer to form the soluble portions of the first photoresist structures causes a solubility-changing agent to diffuse from the first overcoat film to perimeter portions of

the first photoresist structures up to a first diffusion depth; the second photoresist structures and the third photoresist structures have a same width; and the first diffusion depth equals the target width minus half the overage amount.

11. The method of claim 1, further comprising forming the first patterned features on the semiconductor wafer using a photolithography technology, wherein: the first widths are determined according to a photolithography technology used to form the first patterned features; and the target width is less than the first widths.

12. The method of claim 1, wherein widths of the third patterned features are equal and are below a resolution capability of a photolithography technology used to form the first patterned features.

13. The method of claim 1, further comprising using the third patterned features to form sub-resolution features in an underlying layer of the semiconductor wafer.

14. A method, comprising: forming, on a semiconductor wafer by photolithography, first photoresist structures having a first width and first recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width; depositing a first overcoat film; forming, using the first overcoat film, soluble portions of the first photoresist structures; selectively removing the first overcoat film; depositing a second overcoat film; removing portions of the second overcoat film and the soluble portions of the first photoresist structures to define second photoresist structures, first overcoat structures of the second overcoat film, and second recesses in regions previously occupied by the soluble portions of the first photoresist structures, the second photoresist structures having a third width less than the first width, the first overcoat structures having the second width, the second recesses having a fourth width less than the target width; modifying the first overcoat structures to become insoluble for development; depositing a third overcoat film; forming, using the third overcoat film, soluble portions of the first overcoat structures; and selectively removing the third overcoat film and the soluble portions of the first overcoat structures to define third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having a sixth width equal to the target width, and third recesses defined by the third photoresist structures and the second overcoat structures and having a seventh width greater than the fourth width.

15. The method of claim 14, wherein: the fifth width equals the third width; and a lateral depth of the soluble portions of the first photoresist structures equals one half a difference between the first width and the third width.

16. The method of claim 14, wherein: the fifth width is less than the third width; and the method further comprises: forming, using the third overcoat film, soluble portions of the second photoresist structures; and selectively removing, when selectively removing the third overcoat film and the soluble portions of the first overcoat structures, the soluble portions of the second photoresist structures to define the third photoresist structures.

17. The method of claim 14, wherein the fifth width, the sixth width, and the seventh width equal the target width and define a 1:1:1 line-space-line-space pitch ratio.

18. The method of claim 14, wherein: the second overcoat film comprises a polymer resin; and modifying the first overcoat structures to become insoluble for development comprises causing, in response to an activation trigger, a polymer crosslinking reaction to occur in the second overcoat film that renders the first overcoat film insoluble for development in a developer used for selectively removing the third overcoat film and the soluble portions of the first overcoat structures.

19. The method of claim 14, wherein a lateral depth of the soluble portions of the first overcoat structures equals one half a difference between the target width and the second width.

20. The method of claim 14, wherein: a minimum achievable width for the second width is determined according to a photolithography technology used for the photolithography; and the target width is less than the minimum achievable width.

21. A method, comprising: forming, by photolithography, first patterned features on a semiconductor wafer, the first patterned features comprising first photoresist structures having a

first width and first recesses defined by the first photoresist structures and having a second width less than the first width and greater than a target width; forming, using an anti-spacer patterning process, second patterned features on the semiconductor wafer, the second patterned features comprising second photoresist structures having a third width less than the first width, first overcoat structures interspersed between the second photoresist structures, and second recesses defined by the second photoresist structures and the first overcoat structures, the first overcoat structures having the second width, the second recesses having a fourth width less than the target width; and forming, using an acid diffusion process, third patterned features on the semiconductor wafer, the third patterned features comprising third photoresist structures having a fifth width, second overcoat structures interspersed between the third photoresist structures and having the target width, and third recesses defined by the third photoresist structures and the second overcoat structures, portions of the first overcoat structures having been selectively removed using the acid diffusion process to form the second overcoat structures, the third recesses having a sixth width greater than the fourth width.
