

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280985

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

LIN; Yaohuan et al.

METHOD OF MANUFACTURING A PAN AND NON-STICK PAN

Abstract

A method of manufacturing a pan is disclosed. The method includes: preparing a roll of stainless-steel; feeding the stainless-steel plate into a roller for rolling to form a pattern on the stainless-steel plate, where the stainless-steel plate enters into the roller in a entering direction with an angle formed between the entering direction and the horizontal line, and the stainless-steel plate exits from the roller in a exiting direction with an angle formed between the entering direction and the horizontal line; punching a rolled stainless-steel plate to form a pan body; compounding a uniform heating layer and a heating layer on a bottom of the pan body in sequence; sandblasting an inner surface of the pan; spraying the inner surface of the pan; and polishing the inner surface of the pan body to remove the coating on the top surface of each of the ribs.

Inventors: LIN; Yaohuan (Jiangmen, CN), LIN; Huabin (Jiangmen, CN)

Applicant: JIANGMEN BONANZA METALWARE CO., LTD. (Jiangmen, CN)

Family ID: 1000007772243

Assignee: JIANGMEN BONANZA METALWARE CO., LTD. (Jiangmen, CN)

Appl. No.: 18/620792

Filed: March 28, 2024

Foreign Application Priority Data

CN 202410261098.X

Mar. 07, 2024

Publication Classification

Int. Cl.: A47J27/00 (20060101); A47J36/02 (20060101)

U.S. Cl.:

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to Chinese patent application No. 202410261098.X filed Mar. 7, 2024. The contents of this application are incorporated herein by reference in their entirety.

TECHNICAL FIELD

[0002] The present disclosure relates to the field of kitchen utensils, and in particular to a method of manufacturing a pan, and non-stick pan manufactured by using the method of manufacturing a pan.

BACKGROUND

[0003] Currently, non-stick pan on the market is generally equipped with an anti-stick coating on the pan body to prevent food from sticking to the pan body. However, the coating is prone to falling off due to heat and friction with a turner during use, which affects use of non-stick pan and even contaminates food.

[0004] In order to prevent the coating on the non-stick pan from falling off, a non-stick pan with a concave and convex pattern on the inner surface of the pan body has appeared on the market. The concave and convex pattern is mainly arranged on the bottom of the pan body, and inner walls of some pan are also provided with the pattern. The concave parts of the concave and convex pattern are provided with an anti-stick coating, while the top surface of the concave and convex pattern is not provided with a coating. This design reduces the contact area between food and the inner surface of the pan, effectively improves the anti-stick effect, prevents direct contact of the food and turner with the coating, improves the durability of the coating and prevents the coating from falling off. However, the concave and convex pattern on the exiting non-stick pan is mainly formed by stamping or chemical corrosion. In the case that the stamping process is used to process the concave and convex pattern on the pan body, due to the problem of demoulding, the size of the concave and convex pattern obtained by stamping is generally relatively large, and the anti-stick effect is reduced; besides, stamping needs to be done one by one, so the efficiency is relatively low. In the case that chemical etching is used to process the concave and convex pattern in the pan body, the process is complicated, the production cost is high, and the chemical materials used tend to pollute the environment.

[0005] Therefore, it is necessary to propose a new method of manufacturing a pan and a non-stick pan manufactured by using the method of manufacturing a pan.

SUMMARY

[0006] In order to solve one of the technical problems existing in the existing technology, the present disclosure provides a method of manufacturing a pan, in which a pattern in a pan body is formed by rolling, which achieves high production efficiency and good anti-stick effect.

[0007] In addition, the present disclosure also provides a non-stick pan manufactured by using the above method of manufacturing a pan.

[0008] In a first aspect of the present disclosure, an embodiment provides a method of manufacturing a pan, at least including the following steps: [0009] S1, preparing a roll of stainless-steel plate; [0010] S2, feeding the stainless-steel plate to a roller with a convex grain for rolling to form a pattern with a concave and convex structure on a side of the stainless-steel plate, where the pattern includes ribs and grooves, and the stainless-steel plate enters into the roller in a entering direction with an angle formed between the entering direction and a horizontal line, and the stainless-steel plate exits from the roller in a exiting direction with an angle formed between the entering direction and the horizontal line; [0011] S3, punching the rolled stainless-steel plate to

form a shape of a pan body, where the pattern is located on an inner surface of the pan body after punching; [0012] S4, compounding a bottom of the pan body obtained after punching with a uniform heating layer and a heating layer in sequence; [0013] S5, sandblasting part or all of the inner surface of the pan body, so as to form a rough surface on the inner surface of the pan body; [0014] S6, spraying the sandblasted surface in the pan body, so as to form an anti-stick coating on the inner surface of the pan body; and [0015] S7, polishing the sandblasted or sprayed surface in the pan body to remove the coating on a top surface of each of the ribs, so as to expose the stainless-steel on the top surface of each of the ribs.

[0016] The method of manufacturing a pan according to embodiments in the first aspect of the present disclosure at least has the following beneficial effects: the pattern with the concave and convex structure is firstly machined on the stainless-steel plate in a rolling manner, compared with the existing technology, machining the pattern by rolling can avoid the difficulty in demoulding, so that the pattern of smaller size can be made, the anti-stick effect of the pan body is improved, and the rolling manner will not pollute the environment. At the same time, the rolling manner can achieve continuous machining of the fine pattern, improve the production efficiency, save production materials, and improve the product competitiveness.

[0017] According to the method of manufacturing a pan in the first aspect of the present disclosure, in the step S2, a width of a top surface of the rib in the pattern formed after the rolling is 0.15-0.6 mm. Due to the limitations of demoulding technology, the width of the top surface of each of the ribs in the pattern formed by stamping in the existing technology is greater than 0.5 mm, and when the width of the top surface of each of the ribs is less than 0.5 mm, it is difficult to demold after a flat surface is stamped as a whole, and thus it is difficult to implement production. However, the narrower the width of the top surface of each of the ribs is, the smaller the contact area with food is and the better the anti-stick effect is.

[0018] According to the method of manufacturing a pan in the first aspect of the present disclosure, in the above step S2, a depth of each of the grooves in the pattern formed after the rolling is 0.02-0.15 mm.

[0019] According to the method of manufacturing a pan according to the first aspect of the present disclosure, in the step S2, when the depth of each of the grooves to be machined is required to be greater than 0.08 mm, the stainless-steel plate is first fed to a preheating furnace for heating and softening before the stainless-steel plate entering into the roller, and then the softened stainless-steel plate is fed to the roller. The softened stainless-steel plate has higher plasticity and makes the pattern be formed easier by rolling when passing through the roller, thereby reducing the difficulty of machining and improving the product yield rate.

[0020] According to the method of manufacturing a pan in the first aspect of the present disclosure, the temperature inside the preheating furnace is 200° C.-600° C., which effectively softens the stainless-steel material.

[0021] According to the method of manufacturing a pan in the first aspect of the present disclosure, the roller includes a driving roller and a driven roller, and the convex pattern is arranged on a surface of the driving roller.

[0022] According to the method of manufacturing a pan in the first aspect of the present disclosure, a pressure-increasing roller is arranged in the outer side of the roller. Through arrangement of the pressure-increasing roller, the pressure of the roller on the stainless-steel plate is increased, making it easier to roll out the pattern. Further, the diameter of the pressure-increasing roller is greater than the diameter of the roller.

[0023] According to the method of manufacturing a pan in the first aspect of the present disclosure, the angle α formed between the entering direction of the stainless-steel plate when entering into the roller and the horizontal line is 5°-20°. The stainless-steel plate enters into roller with slight inclination, which makes entry of the stainless-steel plate smooth.

[0024] According to the method of manufacturing a pan in the first aspect of the present disclosure,

the angle β formed between the exiting direction of the stainless-steel plate when leaving the roller and the horizontal line is 5°-20°. The stainless-steel plate leaves the roll with slight inclination, which results in a smooth separation of the stainless-steel plate from the roller after the rolling.

[0025] According to the method of manufacturing a pan in the first aspect of the present disclosure, in the pattern formed after the rolling in the above step S2, the top surface and side walls of the rib are perpendicular to each other. Such design can further decrease the width of the top surface, and improve the non-stick effect.

[0026] According to the method of manufacturing a pan in the first aspect of the present disclosure, in the step S2, a width of the groove in the pattern formed after the rolling is 0.1-10 mm.

[0027] According to the method of manufacturing a pan in the first aspect of the present disclosure, in the step S2, the pattern formed after the rolling includes at least one of mesh, honeycomb or a multi-point pattern.

[0028] According to the method of manufacturing a pan in the first aspect of the present disclosure, the heating layer is made of ferritic stainless-steel.

[0029] According to the method of manufacturing a pan in the first aspect of the present disclosure, the uniform heating layer is made of aluminum alloy.

[0030] In a second aspect of the present disclosure, an embodiment provides a non-stick pan, the non-stick pan is manufactured by using the method of manufacturing a pan described in the first aspect of the present disclosure.

[0031] The non-stick pan according to the embodiments of the second aspect of the present disclosure at least has the following beneficial effects: the non-stick pan of the present disclosure is manufactured by using the above-mentioned method of manufacturing a pan, which has high production efficiency and has no problems of demoulding and environmental pollution. At the same time, the produced non-stick pan can have smaller-sized pattern to improve the anti-stick effect of the pan body and improve the competitiveness of the product.

[0032] Additional features and advantages of the present disclosure will be elaborated in the description which follows, and will be partially apparent from the description, or understood by practice of the present disclosure. The objectives and other advantages of the present disclosure can be achieved and obtained by structures particularly pointed out in the description, claims and accompanying drawings.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0033] The accompanying drawings are used to provide a further understanding of the technical solution of the present disclosure and constitute a part of the description. They are used to explain the technical solution of the present disclosure together with the embodiments of the present disclosure and do not constitute a limitation of the technical solution of the present disclosure.

[0034] FIG. 1 is a first embodiment of rolling a stainless-steel plate in a method of manufacturing a pan provided in the first aspect of the present disclosure.

[0035] FIG. 2 is a second embodiment of rolling a stainless-steel plate in the method of manufacturing a pan provided in the first aspect of the present disclosure.

[0036] FIG. 3 is a cross-sectional view of a stainless-steel plate with a pattern obtained after rolling.

[0037] FIG. 4 is a cross-sectional view of a pan body obtained after punching the stainless-steel plate in FIG. 3.

[0038] FIG. 5 is a cross-sectional view of the pan body in FIG. 4 compounded with a uniform heating layer and a heating layer.

[0039] FIG. 6 is a cross-sectional view of the pan body in FIG. 5 after being sandblasted, sprayed

and polished.

[0040] FIG. 7 is a step flow chart of the method of manufacturing a pan provided by the present disclosure.

[0041] FIG. 8 is a schematic structural diagram of a non-stick pan provided in the second aspect of the present disclosure.

[0042] FIG. 9 is a schematic diagram of the non-stick pan in FIG. 8 with a handle.

REFERENCE NUMERALS FOR THE ACCOMPANYING DRAWINGS

[0043] stainless-steel plate roll **10**, stainless-steel plate **11**, roller **20**, driving roller **21**, driven roller **22**, pressure-increasing roller **23**, preheating furnace **30**; [0044] pan body **100**, heating layer **110**, uniform heating layer **120**, pattern **130**, rib **131**, top surface **1311**, side wall **1312**, groove **132**, coating **133**, outer flange **140**, handle **200**.

DETAILED DESCRIPTION

[0045] In order to make the purpose, technical solutions and advantages of the present disclosure clear, the present disclosure will be further described in detail below with reference to the accompanying drawings and embodiments. It should be understood that the specific embodiments described herein are only used to explain the present disclosure and are not used to limit the present disclosure.

[0046] In the description of the present disclosure, it should be noted that, unless otherwise specified and limited, the term “connection” should be understood in a broad sense, for example, it can be a fixed connection or a movable connection, a detachable connection or a non-detachable connection, or an integrated connection; it can be a mechanical connection, an electrical connection, or communication with each other; it can be directly connection, or indirectly connection through an intermediate medium or structure; and it can be an internal connection, an indirect connection, or an interactive relationship between two elements.

[0047] In the description of the present disclosure, it should be noted that “several” means one or more, “plural (or multiple)” means more than two; “greater than, less than, over, etc.” are understood to exclude the original number; and “above, below, within, etc.” are understood to include the original number. The description of “first”, “second”, etc. is only for the purpose of distinguishing technical features, and cannot be understood as indicating or implying relative importance or implying the quantity or order of the indicated technical features.

[0048] The embodiments of the present disclosure will be further described below with reference to FIGS. 1 to 9.

[0049] Referring to FIGS. 1 to 7, a first aspect of the present disclosure provides a method of manufacturing a pan, which at least includes the following steps:

[0050] S1. A roll of stainless-steel plate **11** is prepared.

[0051] S2. As shown in FIG. 1, the stainless-steel plate **11** is fed into a roller **20** for rolling. A surface of the roller **20** is provided with a convex grain. The stainless-steel plate **11** enters into the roller **20** in a entering direction with an angle formed between the entering direction and a horizontal line, and the stainless-steel plate **11** exits from the roller **20** in a exiting direction with an angle formed between the entering direction and the horizontal line. A pattern **130** with a concave and convex structure is formed on a side of the stainless-steel plate **11** by means of the rolling. As shown in FIG. 3, the pattern **130** includes ribs **131** and grooves **132**.

[0052] S3. As shown in FIG. 4, the rolled stainless-steel plate **11** is punched to form a shape of a pan body **100**, and the pattern **130** is located on an inner surface of the pan body **100** after punching.

[0053] S4. As shown in FIG. 5, a bottom of the pan body **100** obtained after punching is sequentially compounded with a uniform heating layer **120** and a heating layer **110**.

[0054] S5. Part or all of the inner surface of the pan body **100** is sandblasted to form a rough surface on the inner surface of the pan body **100**.

[0055] S6. The sandblasted surface of the pan body **100** is sprayed to form an anti-stick coating **133**

on the inner surface of the pan body **100**.

[0056] S7. The sandblasted or spray-coated surface of the pan body **100** is polished to remove the coating **133** on the top surface of each of the ribs **131**, so that stainless-steel is exposed on the top surface of each of the ribs **131** as shown in FIG. 6, and the pan is obtained.

[0057] Further, in the step S2, in the pattern **130** formed after the rolling, the width of the top surface **1311** of the rib is 0.15-0.6 mm. However, due to the limitations of demoulding technology, the width of the top surface of each of the ribs of a pattern formed by stamping in the existing technology is greater than 0.5 mm, when the width of the top surface **1311** of the rib is less than 0.5 mm, it is difficult to demold after the flat surface is stamped as a whole, making it difficult to implement production. According to the present disclosure, rolling is used to form the pattern **130** on the surface of the stainless-steel plate **11** to avoid the problem of demoulding. Therefore, the width of the top surface of each of the ribs **1311** can be made into a smaller size, and the narrower the width of the top surface of each of the ribs **1311** is, the smaller the contact area with food is and the better the anti-stick effect is.

[0058] Further, in the step S2, in the pattern formed after the rolling, the depth of each of the grooves **132** is 0.02-0.15 mm, and the depth of each of the grooves **132** can be flexibly set according to the size of the product itself and practical requirements. The depth of each of the grooves **132** also affects the sequence of processes of manufacturing the pan. Specifically, as shown in FIG. 1, when the depth of each of the grooves **132** to be machined is required to be less than 0.08 mm, the stainless-steel plate **11** directly enters into the roller **20** for rolling; and as shown in FIG. 2, when the depth of each of the grooves to be machined is required to be greater than 0.08 mm, before entering into the roller **20**, the stainless-steel plate **11** is first fed to the preheating furnace **30** for heating. The temperature inside the preheating furnace **30** is 200° C.-600° C. Through heating in the preheating furnace **30**, the stainless-steel plate **11** is softened, and then the softened stainless-steel plate **11** is fed to the roller **20**. The softened stainless-steel plate **11** has better plasticity and makes rolling of the pattern easier when passing through the roller **20**, thereby reducing the difficulty of machining and improving the product yield rate.

[0059] Further, in the step S2, the angle α formed between the entering direction and the horizontal line upon the condition that the stainless-steel plate **11** enters into the roller **20** is 5°-20°, and the angle β formed between the exiting direction and the horizontal line upon the condition that the stainless-steel plate **11** exits from the roller **20** is 5°-20°. As shown in FIGS. 1 and 2, the stainless-steel plate **11** enters and exits from the roller **20** with slight inclination, which makes entry of the stainless-steel plate **11** smooth, as well as results in a smooth separation of the stainless-steel plate **11** from the roller **20** after the rolling.

[0060] Further, as shown in FIGS. 1 and 2, in the above step S2, the roller **20** includes a driving roller **21** and a driven roller **22**, and the convex pattern is provided on the surface of the driving roller **21**. A pressure-increasing roller **23** is also provided in the outer side of the roller **20**. The diameter of the pressure-increasing roller **23** is larger than the diameter of the roller **20**. Through setting of the pressure-increasing roller **23**, the pressure of the roller **20** on the stainless-steel plate is increased. The diameter of the roller **20** is smaller, so that the contact area between the roller **20** and the pressure-increasing roller **23** as well as the stainless-steel plate **11** is reduced, thereby increasing the pressure intensity, and making it easier to roll out the pattern.

[0061] Further, in the above step S2, in the pattern **130** formed after the rolling, the top surface **1311** and the side walls **1312** of the rib **131** are perpendicular to each other, and the width of the groove **132** is 0.1-10 mm. Such design can further reduce the width of the top surface **1311** and improve the non-stick effect.

[0062] Furthermore, in the step S2, the pattern **130** formed after the rolling preferably includes at least one of a mesh shape, a honeycomb shape, or a multi-point pattern.

[0063] Further, in the above step S4, the compounded heating layer **110** is made of ferritic stainless-steel and can be heated by induction; and the uniform heating layer **120** is made of

aluminum alloy and has high thermal conductivity. The uniform heating layer **120** preferably covers the bottom of the pan body **100** evenly, so that the bottom of the pan body **100** is evenly heated through the heat conduction of the uniform heating layer **120**.

[0064] Furthermore, in the step **S5**, sandblasting can be performed with a brown emery abrasive (a-type alumina). For the formed rough surface, the following roughness parameters are required: $Ra \geq 2$ microns, preferably $3 \text{ microns} \leq Ra \leq 5 \text{ microns}$, and $Rz \geq 25$ microns, preferably $30 \text{ microns} \leq Rz \leq 50 \text{ microns}$. The rough surface in such roughness can make the subsequently sprayed coating **133** have better adhesion and prevent the coating **133** from falling off during use.

[0065] Furthermore, in the step **S6**, a spray gun can be used to spray the inner surface of the pan body **100** to form the anti-stick coating **133** on the inner surface of the pan body **100**.

[0066] Furthermore, it is easy to understand that during the machining steps of the above method of manufacturing a pan or after completing the above steps, additional machining steps can be added according to actual needs, such as machining the upper edge of the pan body **100** to form an outer flange **140**, and polish the surface of the outer flange **140** to form a smooth surface on the top of the outer flange **140**. A handle **200** can also be installed on the pan body **100** through other processes.

[0067] Referring to FIGS. **8** and **9**, a second aspect of the present disclosure provides a non-stick pan, which is manufactured by using the method of manufacturing a pan of the first aspect of the present disclosure. Specifically, the non-stick pan includes a pan body **100**. The pan body **100** is made of a stainless-steel plate **11** that has been rolled first. A side of the stainless-steel plate **11** forms a pattern **130** during the rolling. When the pan body **100** is formed, the pattern **130** is arranged on an inner surface of the pan body **100**. A heating layer **110** for induction heating is arranged at a bottom of the pan body **100**. A uniform heating layer **120** is arranged between the pan body **100** and the heating layer **110**. The inner surface of the pan body **100** is also provided with an anti-stick coating **133**. The coating **133** is distributed in grooves **132**. The excess coating **133** is removed from the top surface **1311** of ribs by polishing, so that the top surface **1311** of the ribs is not covered by the coating **133**, as shown in FIG. **6**. Furthermore, an outer flange **140** is arranged in the upper edge of the pan body **100**. A top of the outer flange **140** is polished to remove the pattern **130** to form a smooth surface. A handle **200** is also installed on an outer wall of the pan body **100**.

[0068] According to the method of manufacturing a pan provided by the present disclosure, the pattern **130** with a concave and convex structure is firstly machined on the stainless-steel plate **11** by rolling. Compared with the existing technology, machining the pattern **130** by rolling can avoid the difficult in demoulding, so that the pattern **130** of smaller size can be made, the anti-stick effect of the pan body **100** is improved, and the rolling manner will not pollute the environment. At the same time, the rolling manner can achieve continuous machining of the fine pattern **130**, improve production efficiency, and save production materials. The non-stick pan made by using the above method of manufacturing a pan has high production efficiency, and can be used to make smaller-sized patterns, thereby improving the anti-stick effect of the pan body **100**, and improving the competitiveness of the product.

[0069] The above is a detailed description of the preferred implementation of the present disclosure, but the present disclosure is not limited to the above-mentioned embodiments. Those skilled in the art can also make various equivalent modifications or substitutions without departing from the gist of the present disclosure. These equivalent modifications or substitutions are all included within the scope defined by the claims of this disclosure.

Claims

1. A method of manufacturing a pan, comprising: **S1**, preparing a roll of stainless-steel plate; **S2**, feeding the stainless-steel plate to a roller with a convex grain for rolling to form a pattern with a concave and convex structure on a side of the stainless-steel plate, wherein the pattern comprises ribs and grooves, the stainless-steel plate enters into the roller in a entering direction with an angle

formed between the entering direction and a horizontal line, and the stainless-steel plate exits from the roller in a exiting direction with an angle formed between the entering direction and a horizontal line; S3, punching the rolled stainless-steel plate to form a shape of a pan body, wherein the pattern is located on an inner surface of the pan body after punching; S4, compounding a bottom of the pan body obtained after punching with a uniform heating layer and a heating layer in sequence; S5, sandblasting part or all of the inner surface of the pan body to form a rough surface on the inner surface of the pan body; S6, spraying the sandblasted surface in the pan body to form an anti-stick coating on the inner surface of the pan body; and S7, polishing the sandblasted or sprayed surface in the pan body to remove the coating on a top surface of each of the ribs, so as to expose stainless-steel on the top surface of each of the ribs.

2. The method of manufacturing a pan according to claim 1, in step S2, a width of the top surface of each of the ribs in the pattern formed after the rolling is 0.15-0.6 mm.

3. The method of manufacturing a pan according to claim 1, in step S2, a depth of each of the grooves in the pattern formed after the rolling is 0.02-0.15 mm.

4. The method of manufacturing a pan according to claim 3, in step S2, upon a condition that the depth of each of the grooves to be machined is required to be greater than 0.08 mm, feeding the stainless-steel plate to a preheating furnace for heating and softening before the stainless-steel plate entering into the roller, and then feeding the softened stainless-steel plate to the roller.

5. The method of manufacturing a pan according to claim 4, wherein a temperature inside the preheating furnace is 200° C.-600° C.

6. The method of manufacturing a pan according to claim 1, wherein the angle α formed between the entering direction and the horizontal line upon the condition that the stainless-steel plate enters into the roller is 5°-20°.

7. The method of manufacturing a pan according to claim 1, wherein the angle β formed between the exiting direction and the horizontal line upon the condition that the stainless-steel plate exits from the roller is 5°-20°.

8. The method of manufacturing a pan according to claim 1, wherein the heating layer is made of ferritic stainless-steel.

9. The method of manufacturing a pan according to claim 1, wherein the uniform heating layer is made of aluminum alloy.
